

Specification data sheet

Page: 1/2

BASF Specification data sheet

Date / Revised: 2010/05/26

Product: **Kaurit® Glue 385**

Version: 1.0

(30034926/SPE_GEN_P/EN)

Date of print 18.11.2025

1. Substance/preparation and company identification

Kaurit® Glue 385

2. Characterization

aminoplastic resin based on: urea, formaldehyde

3. Specified tests

Property	Test method (parameter)	Value
Solid content	DIN EN ISO 3251	64.5 - 66.5 %
pH value	DIN ISO 976 (20 °C)	7.5 - 9.5
Viscosity, dynamic	DIN EN ISO 3219, Annex B (20 °C)	600 - 800 mPa.s
Density	ISO 2811-3 (20 °C)	1.29 - 1.30 g/cm ³

4. Handling and Storage

Advice on safe handling:

Handle in accordance with good industrial hygiene and safety practice.

BASF Specification data sheet
Date / Revised: 2010/05/26
Product: **Kaurit® Glue 385**

Version: 1.0

(30034926/SPE_GEN_P/EN)

Date of print 18.11.2025

Storage stability:

2.5 - 3.5 Months at 20 °C

Limit viscosity: 10.000 mPa.s

3 - 4 Week at 30 °C

Limit viscosity: 10.000 mPa.s

Further information on storage conditions:

Keep in a cool place.

Vertical lines in the left hand margin indicate an amendment from the previous version.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

This product specification was issued automatically and is not signed.