

Specification data sheet

Page: 1/2

BASF Specification data sheet

Date / Revised: 2026/01/23

Product: **Epotal® CF 522 X**

Version: 1.0

(30864374/SPE_GEN_P/EN)

Date of print 02.02.2026

1. Substance/preparation and company identification

Epotal® CF 522 X

BASF SE

Regional Business Unit Dispersions Europe

67056 Ludwigshafen, Germany

E-mail address: ede-qm@basf.com

2. Characterization

Aqueous dispersion of a polymer based on: acrylic ester, Styrene

polyurethane

3. Specified tests

Property	Test method (parameter)	Value
Solid content	DIN EN ISO 3251	44.0 - 46.0 %
pH value	DIN ISO 976	5.5 - 8.5
Viscosity, dynamic	DIN EN ISO 3219 (23 °C, 250 1/s)	5 - 200 mPa.s

4. Handling and Storage

Advice on safe handling:

See SDS section 7 - Handling and storage.

Storage stability:

at 10 - 30 °C

BASF Specification data sheet

Date / Revised: 2026/01/23

Product: **Epotal® CF 522 X**

Version: 1.0

(30864374/SPE_GEN_P/EN)

Date of print 02.02.2026

Vertical lines in the left hand margin indicate an amendment from the previous version.

The Specified Parameters listed in section 3 represent the contractual quality at the time of the transfer of risk. The data are controlled at regular intervals as part of our quality assurance program. BASF MAKES NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, BY FACT OR LAW, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

This product specification was issued automatically and is not signed.