

Specification data sheet

Page: 1/2

BASF Specification data sheet

Date / Revised: 2026/02/13

Product: **Laromer® PO 8997 E**

Version: 1.0

(30863155/SPE_GEN_P/EN)

Date of print 14.02.2026

1. Substance/preparation and company identification

Laromer® PO 8997 E

BASF SE

Global Business Unit Resins and Additives

67056 Ludwigshafen, Germany

E-mail address: ede-qm@basf.com

2. Characterization

Polymer based on: polyetherpolyol, acrylic ester, modified

Form: liquid

3. Specified tests

Property	Test method (parameter)	Value
Viscosity, dynamic	DIN EN ISO 3219 (23 °C, 250 1/s)	300 - 500 mPa.s
Iodine colour value	DIN EN 1557	< 1.1
Acid number (KOH)	DIN EN ISO 2114	<= 0.5 mg/g

4. Handling and Storage

Advice on safe handling:

See SDS section 7 - Handling and storage.

Storage stability:

<= 6 Months at <= 35 °C

Vertical lines in the left hand margin indicate an amendment from the previous version.

BASF Specification data sheet
Date / Revised: 2026/02/13
Product: **Laromer® PO 8997 E**

Version: 1.0

(30863155/SPE_GEN_P/EN)

Date of print 14.02.2026

The Specified Parameters listed in section 3 represent the contractual quality at the time of the transfer of risk. The data are controlled at regular intervals as part of our quality assurance program. BASF MAKES NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, BY FACT OR LAW, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

This product specification was issued automatically and is not signed.