

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12389875
Kind Code	B2
Date of Patent	August 19, 2025
Inventor(s)	Huck; Nathan Foster et al.

Low density pet litters and methods of making and using such pet litters

Abstract

Compacting expanded perlite fines in the presence of a small amount of binder (starch and/or clay) and water, followed by drying, produces particles with low density, good integrity, and surprisingly higher absorption by volume than non-compacted expanded perlite or non-swelling clay. Furthermore, addition of a small amount of clumping agent (e.g., guar gum) to the compacted granules results in a clumping litter with low density, good integrity and comparable clumping ability to traditional clay clumping litter.

Inventors: Huck; Nathan Foster (Jackson, MO), Muscroft; Colin (Glen Carbon, IL), Leinart; David Odell (Ballwin, MO)

Applicant: Société des Produits Nestlé S.A. (Vevey, CH)

Family ID: 1000008767361

Assignee: SOCIÉTÉ DES PRODUITS NESTLÉ S.A. (Vevey, CH)

Appl. No.: 17/109012

Filed: December 01, 2020

Prior Publication Data

Document Identifier	Publication Date
US 20210076635 A1	Mar. 18, 2021

Related U.S. Application Data

division parent-doc US 15298971 20161020 US 10881077 child-doc US 17109012
us-provisional-application US 62245349 20151023

Publication Classification

Int. Cl.: **A01K1/015** (20060101); **A01K1/01** (20060101); **B01J20/10** (20060101); **B01J20/12** (20060101); **B01J20/20** (20060101); **B01J20/24** (20060101); **B01J20/28** (20060101); **B01J20/30** (20060101)

U.S. Cl.:

CPC **A01K1/0154** (20130101); **A01K1/0107** (20130101); **A01K1/0152** (20130101); **A01K1/0155** (20130101); **B01J20/106** (20130101); **B01J20/12** (20130101); **B01J20/20** (20130101); **B01J20/24** (20130101); **B01J20/28011** (20130101); **B01J20/28016** (20130101); **B01J20/3021** (20130101); **B01J20/3035** (20130101); **B01J20/3042** (20130101);

Field of Classification Search

CPC: A01K (1/0152); A01K (1/0154); A01K (1/0155)

USPC: 119/171-173

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
3993498	12/1975	Koekemoer	N/A	N/A
5152250	12/1991	Loeb	N/A	N/A
5193489	12/1992	Hardin	N/A	N/A
5303676	12/1993	Lawson	N/A	N/A
5359961	12/1993	Goss	N/A	N/A
5421291	12/1994	Lawson	N/A	N/A
5526770	12/1995	Kiebke	N/A	N/A
5609123	12/1996	Luke	N/A	N/A
5634431	12/1996	Reddy	N/A	N/A
5638770	12/1996	Peleties	N/A	N/A
5655480	12/1996	Steckel	N/A	N/A
5664523	12/1996	Ochi	N/A	N/A
5724915	12/1997	Ochi	N/A	N/A
5826543	12/1997	Raymond	N/A	N/A
5836263	12/1997	Goss	N/A	N/A
5927049	12/1998	Simard	N/A	N/A
5960743	12/1998	Taylor	N/A	N/A
5961968	12/1998	Moore	N/A	N/A
5992351	12/1998	Jenkins	N/A	N/A
6014947	12/1999	Sladek	N/A	N/A
6053125	12/1999	Kory	N/A	N/A
6089190	12/1999	Jaffee	N/A	N/A
6101978	12/1999	Steckel	N/A	N/A
6276300	12/2000	Lewis	N/A	N/A
6287550	12/2000	Trinh	N/A	N/A

6308658	12/2000	Steckel	N/A	N/A
6346240	12/2001	Moore	N/A	N/A
6568349	12/2002	Hughes	N/A	N/A
6657098	12/2002	Niki	N/A	N/A
6745720	12/2003	Rasner	N/A	N/A
6868802	12/2004	McPherson	N/A	N/A
7011824	12/2005	Moore	N/A	N/A
7041279	12/2005	Ali	N/A	N/A
7316201	12/2007	Rasner	N/A	N/A
7343874	12/2007	DeLeeuw	N/A	N/A
7467600	12/2007	Ikegami	N/A	N/A
7595429	12/2008	Hursey	N/A	N/A
7603964	12/2008	Jenkins	N/A	N/A
7665418	12/2009	Bracilovic	N/A	N/A
7753002	12/2009	Wang	N/A	N/A
8074604	12/2010	Swank	N/A	N/A
8096267	12/2011	Greene	N/A	N/A
8252344	12/2011	Hursey	N/A	N/A
8268018	12/2011	Privitera	N/A	N/A
8429849	12/2012	Bertin	N/A	N/A
8453604	12/2012	Matsuo	N/A	N/A
8490578	12/2012	Hughes	N/A	N/A
8955294	12/2014	Free	N/A	N/A
9547000	12/2016	Gravel-Lacroix et al.	N/A	N/A
9986714	12/2017	Huck	N/A	N/A
2005/0005870	12/2004	Fritter	N/A	N/A
2005/0056229	12/2004	Greene	N/A	N/A
2005/0175577	12/2004	Jenkins	424/76.1	B01J 20/12
2006/0042515	12/2005	Bodycomb et al.	N/A	N/A
2006/0065200	12/2005	Jenkins	N/A	N/A
2006/0243212	12/2005	Jenkins	N/A	N/A
2007/0169709	12/2006	Wang	119/173	B03C 1/0332
2007/0289543	12/2006	Petska et al.	N/A	N/A
2008/0022940	12/2007	Kirsch et al.	N/A	N/A
2008/0029039	12/2007	Jenkins	N/A	N/A
2008/0223302	12/2007	Wang	N/A	N/A
2008/0251027	12/2007	Kirsch et al.	N/A	N/A
2009/0217882	12/2008	Jenkins	N/A	N/A
2010/0107931	12/2009	Roulston	N/A	N/A
2011/0123474	12/2010	Jenkins et al.	N/A	N/A
2011/0174228	12/2010	Liu	N/A	N/A
2012/0118242	12/2011	Cheeseman	N/A	N/A
2014/0174370	12/2013	Huck	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2005202838	12/2005	AU	N/A

2546538	12/2006	CA	A01K 1/0152
2546538	12/2012	CA	A01K 1/0152
4312279	12/1993	DE	N/A
4427334	12/1995	DE	N/A
1353548	12/2004	EP	N/A
1139726	12/2005	EP	N/A
2318495	12/1997	GB	N/A
H10225633	12/1997	JP	N/A
04649707	12/1999	JP	N/A
04175726	12/1999	JP	N/A
2003019190	12/2002	JP	N/A
2003116389	12/2002	JP	N/A
2004514438	12/2003	JP	N/A
05183166	12/2008	JP	N/A
1998083194	12/2004	KR	N/A
2158078	12/1999	RU	N/A
2422829	12/2010	RU	N/A
2503174	12/2013	RU	N/A
2510167	12/2013	RU	N/A
WO-9956869	12/1998	WO	B01J 20/043
2001050843	12/2000	WO	N/A
201107861	12/2011	ZA	N/A

OTHER PUBLICATIONS

International Search Report and Written Opinion for PCT Application No. PCT/IB16/095005 dated Feb. 21, 2017. cited by applicant

International Search Report and Written Opinion for PCT Application No. PCT/IB016/095006 dated Feb. 21, 2017. cited by applicant

International Search Report and Written Opinion for PCT Application No. PCT/US2013/077396 dated Mar. 17, 2014. cited by applicant

Extended European search report to application No. 22176829.4 dated Sep. 28, 2022. cited by applicant

Primary Examiner: Poon; Peter M

Assistant Examiner: Clerkley; Danielle A

Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS (1) This application is a divisional of U.S. application Ser. No. 15/298971 filed Oct. 20, 2016, which claims priority to U.S. Provisional Application No. 62/245349 filed Oct. 23, 2015, the disclosure of which is incorporated by references in its entirety.

BACKGROUND

(1) The present disclosure relates generally to a low density absorbent material which can be used in both clumping and non-clumping pet litter. More specifically, the present disclosure is directed to low density pet litters comprising compacted particles of expanded perlite and methods for making and using such pet litters

(2) Litter boxes are used by pets such as cats for elimination of urine and fecal matter. A litter box contains a layer of pet litter that receives the urine and fecal matter. The pet litter is granular, absorbent and either non-clumping or clumping. A clumping pet litter is a litter product in which the particles facilitate formation of clumps after the urine and fecal matter is deposited in the pet litter. The clumps are typically sifted from the litter box using a litter scoop and then discarded. Non-clumping pet litter is typically better at absorbing urine and thus removing urine odors, but replacing soiled non-clumping pet litter without emptying the entire box of litter can be difficult.

(3) Consumers fill their litter boxes based on volume, so litters should be highly absorbent by volume. However, traditional absorbent litters are bulky and dense, and thus packages of such litters are heavy and difficult to handle.

(4) Existing litters include compositions made from clay minerals, silica gel, and agricultural wastes. Clay minerals are absorptive but also heavy. Silica gel is also absorptive, but the commonly used aggregate shape and size can have poor cat acceptance, which can lead to house soiling and/or a risk of urinary minerals aggregating into stones or crystalizing in a cat. Agricultural wastes are also absorptive, but many are in pellet form and can have poor animal acceptance. Agricultural waste litters, due to their composition, may also serve as food source and thus support growth of odor causing microorganisms in the litter box.

(5) U.S. Pat. No. 5,655,480 to Steckel et al. discloses an animal control litter comprised of a clumping agent, a surfactant, an odor control agent and light weight aggregate expanded to form porous surfaces by subjecting the aggregate to a temperature of 1,800° F. This litter has a density between 5 and 10 lb/ft.^{sup.3}. However, the material is less absorptive by volume than clay. Additionally, the expanded perlite aggregate material is fragile and can break down easily. The material may also be “too light” for good cat acceptance.

SUMMARY

(6) The present disclosure relates to low density pet litters comprising compacted particles of expanded perlite, preferably having a diameter smaller than 30 mesh (that is, a diameter smaller than 595 microns) and preferably as the primary ingredient in the litter. As a non-limiting example, about 95% or more of the perlite fines in the compacted particles can have a diameter smaller than 30 mesh (that is, a diameter smaller than 595 microns) and no greater than about 5% of the compacted particles can be up to 4 mesh (that is, have a diameter greater than 4.76 mm).

(7) The present inventors unexpectedly found that compacting expanded perlite fines in the presence of a small amount of starch and water, followed by drying, produces particles with low density, good integrity, and surprisingly higher absorption by volume than non-compacted expanded perlite or non-swelling clay. Furthermore, addition of a small amount of clumping agent (e.g., guar gum) to the compacted granules results in a clumping litter with low density, good integrity and comparable clumping ability to traditional clay clumping litter.

(8) Accordingly, in a general embodiment, the present disclosure provides a method of making a pet litter. The method comprises: compacting a material comprising expanded perlite fines to form a compacted material comprising expanded perlite; breaking the compacted material comprising expanded perlite to form particles of the compacted material comprising expanded perlite; separating the particles which have a size within a predetermined size range from a remainder of the particles; drying the particles which have the size within the predetermined size range; and using the dried particles as at least a portion of the pet litter. In another embodiment, the present disclosure provides a pet litter made by this method.

(9) In an embodiment, the expanded perlite fines have a size not greater than about 600 microns. In one embodiment, the expanded perlite fines have a diameter from about 50 microns to about 600 microns, alternatively from about 100 microns to about 550 microns, alternatively from about 150 microns to about 500 microns, alternatively from about 200 microns to about 450 microns, alternatively from about 250 microns to about 400 microns, alternatively from about 300 microns to about 350 microns.

- (10) In one embodiment, the breaking of the compacted material comprising expanded perlite fines and/or drying are optional.
- (11) In an embodiment, the compacting is performed at a pressure from about 500 psi (3447 kPa) to about 1,300 psi (8963.18 kPa).
- (12) In an embodiment, the material comprises about 0.25 wt % to about 5.0 wt % of a binder. The binder can be starch (e.g., pre-gelled cereal starch) and/or clay. At least a portion of the binder can be added to the expanded perlite fines as a dry mix before the compacting of the material. At least a portion of the binder can be pre-blended with water and then added to the expanded perlite fines before the compacting of the material.
- (13) In an embodiment, the water in the material comprises about 15.0 wt % to about 25.0 wt % of water.
- (14) In an embodiment, the material comprises about 50 wt % to about 85 wt % of the expanded perlite fines.
- (15) In an embodiment, the predetermined size range is about 595 microns to about 2,380 microns.
- (16) In an embodiment, the particles are dried to a moisture content of about 0.25 wt % to about 10.0 wt %.
- (17) In another embodiment, the present disclosure provides a pet litter comprising dried particles of compacted material comprising expanded perlite, the particles having a density of about 25.0 lb/ft.³ to about 45.0 lb/ft.³, preferably about 30.0 lb/ft.³ to about 42.0 lb/ft.³.
- (18) In an embodiment, the litter is a non-clumping litter that does not contain a clumping agent.
- (19) In an embodiment, the litter is a clumping litter comprising a clumping agent. The clumping agent can be selected from the group consisting of bentonite, guar gum, starches, xanthan gum, gum Arabic, gum acacia, silica gel, and mixtures thereof.
- (20) In an embodiment, the pet litter further comprises an additive selected from the group consisting of an odor control agent, a fragrance, an anti-microbial agent, an anti-sticking agent, an agent for controlling pH, a dye, a coloring agent, a de-dusting agent, a disinfectant, and combinations thereof. An odor control agent can be carbon, particularly activated carbon.
- (21) In another embodiment, the present disclosure provides a method of managing animal waste. The method comprises using pet litter comprising dried particles of compacted material comprising expanded perlite, the particles having a density of about 25.0 lb/ft.³ to about 45.0 lb/ft.³ (preferably about 30.0 lb/ft.³ to about 42.0 lb/ft.³) in a litter box.
- (22) In another embodiment, the present disclosure provides a method of treating out-of-box elimination of a pet. The method comprises using pet litter comprising dried particles of compacted material comprising expanded perlite, the particles having a density of about 25.0 lb/ft.³ to about 45.0 lb/ft.³ (preferably about 30.0 lb/ft.³ to about 42.0 lb/ft.³) in a litter box located in a building in which the pet resides.
- (23) In another embodiment, the present disclosure provides a method of treating, preventing or reducing the risk of a lower urinary tract disease in a cat. The method comprises using pet litter comprising dried particles of compacted material comprising expanded perlite, the particles having a density of about 25.0 lb/ft.³ to about 45.0 lb/ft.³ (preferably about 30.0 lb/ft.³ to about 42.0 lb/ft.³) in a litter box located in a building in which the cat resides.
- (24) An advantage of one or more embodiments provided by the present disclosure is to provide improved pet litters.
- (25) Another advantage of the present disclosure is to provide methods of making improved pet litters.
- (26) A further advantage of the present disclosure is to provide pet litters that have a low density without sacrificing particle integrity or absorptive performance.
- (27) Still another advantage of the present disclosure is to provide pet litters that have both a low density and good pet acceptance.
- (28) Yet another advantage of the present disclosure is to enable lighter packages of pet litter

without decreasing the volume thereof.

(29) Another advantage of the present disclosure is to enable a pet owner to more easily purchase, transport and utilize a package of pet litter.

(30) A further advantage of the present disclosure is to provide a low density granular absorbent with good particle integrity and having surprisingly improved absorption relative to traditional clay litter and the pre-processed principal raw material.

(31) Still another advantage of the present disclosure is to provide a material that can be used as an improved non-clumping pet litter or employed in a formulation for an improved clumping pet litter.

(32) Additional features and advantages are described herein and will be apparent from the following Detailed Description.

Description

DETAILED DESCRIPTION

(1) As used in this disclosure and the appended claims, the singular forms “a,” “an” and “the” include plural referents unless the context clearly dictates otherwise. Thus, for example, reference to “a material” or “the material” includes two or more materials.

(2) The words “comprise,” “comprises” and “comprising” are to be interpreted inclusively rather than exclusively. Likewise, the terms “include,” “including” and “or” should all be construed to be inclusive, unless such a construction is clearly prohibited from the context.

(3) However, the devices and compositions disclosed herein may lack any element that is not specifically disclosed. Thus, a disclosure of an embodiment using the term “comprising” includes a disclosure of embodiments “consisting essentially of” and “consisting of” the components identified. Similarly, the methods disclosed herein may lack any step that is not specifically disclosed herein. Thus, a disclosure of an embodiment using the term “comprising” includes a disclosure of embodiments “consisting essentially of” and “consisting of” the steps identified. “Consisting essentially of” means that the embodiment comprises more than 50% of the identified components, preferably at least 75% of the identified components, more preferably at least 85% of the identified components, most preferably at least 95% of the identified components, for example at least 99% of the identified components.

(4) The term “and/or” used in the context of “X and/or Y” should be interpreted as “X,” or “Y,” or “X and Y.” Where used herein, the terms “example” and “such as,” particularly when followed by a listing of terms, are merely exemplary and illustrative and should not be deemed to be exclusive or comprehensive. Any embodiment disclosed herein can be combined with any other embodiment disclosed herein unless explicitly stated otherwise.

(5) All percentages expressed herein are by weight of the total weight of the composition unless expressed otherwise. As used herein, “about” and “approximately” are understood to refer to numbers in a range of numerals, for example the range of -10% to +10% of the referenced number, preferably within -5% to +5% of the referenced number, more preferably within -1% to +1% of the referenced number, most preferably within -0.1% to +0.1% of the referenced number. All numerical ranges herein should be understood to include all integers, whole or fractions, within the range. Moreover, these numerical ranges should be construed as providing support for a claim directed to any number or subset of numbers in that range. For example, a disclosure of from 1 to 10 should be construed as supporting a range of from 1 to 8, from 3 to 7, from 1 to 9, from 3.6 to 4.6, from 3.5 to 9.9, and so forth.

(6) Numerical adjectives, such as “first” and “second,” are merely used to distinguish components. These numerical adjectives do not imply the presence of other components, a relative positioning, or any chronological implementation. In this regard, the presence of a “second widget” does not imply that a “first widget” is necessarily present. Further in this regard, a “second widget” can be

used before, after, or simultaneously with any “first widget.”

(7) The terms “pet” and “animal” are used synonymously herein and mean any animal which can use a litter box, non-limiting examples of which include a cat, a dog, a rat, a ferret, a hamster, a rabbit, an iguana, a pig or a bird. The pet can be any suitable animal, and the present disclosure is not limited to a specific pet animal. The term “elimination” means urination and/or defecation by a pet.

(8) As used herein, the term “litter” means any substance that can absorb animal urine and/or decrease odor from animal urine and/or feces. A “clumping litter” forms aggregates in the presence of moisture, the aggregates distinct from the other litter in the litter box. A “non-clumping litter” does not form distinct aggregates.

(9) The term “litter box” means any apparatus that can hold pet litter, for example a container with a bottom wall and one or more side walls, and/or any apparatus configured for litter to be positioned thereon, for example a mat or a grate. As a non-limiting example, a litter box may be a rectangular box having side walls that have a height of at least about six inches.

(10) The term “mesh” is defined by the ASTM E-11 U.S.A. standard specification for sieves. As used herein, “size” of a particle refers to the length of the longest dimension of the particle.

(11) The methods and devices and other advances disclosed herein are not limited to particular methodologies, protocols, and reagents because, as the skilled artisan will appreciate, they may vary. Further, the terminology used herein is for the purpose of describing particular embodiments only and does not limit the scope of that which is disclosed or claimed.

(12) Unless defined otherwise, all technical and scientific terms, terms of art, and acronyms used herein have the meanings commonly understood by one of ordinary skill in the art in the field(s) of the present disclosure or in the field(s) where the term is used. Although any compositions, methods, articles of manufacture, or other means or materials similar or equivalent to those described herein can be used, the preferred devices, methods, articles of manufacture, or other means or materials are described herein.

(13) An aspect of the present disclosure is a method of making a pet litter. The method can comprise compacting a material comprising expanded perlite fines, a binder and water, for example using compacting rolls.

(14) The compacting can be performed at a compaction roll back-pressure of at least about 500 psi (3447 kPa), for example about 500 psi (3447 kPa) to about 1,300 psi (8963.18 kPa), such as about 500 psi (3447 kPa) to about 800 psi (5516 kPa) or about 800 psi (5516 kPa) to about 1,300 psi (8963.18 kPa). The size of the expanded perlite fines is preferably not greater than about 30 mesh (that is, having a diameter not greater than 595 microns). As a non-limiting example, about 95% or more of the perlite fines in the compacted particles can be smaller than 30 mesh (that is, having a diameter smaller than 595 microns) and no greater than about 5% of the compacted particles can be up to 4 mesh (that is, having a diameter greater than 4.76 mm). In an embodiment, the expanded perlite fines comprise particles eliminated in step 101 of the method 100 disclosed in U.S. Patent App. Pub. No. 2014/0174370 to Huck et al., herein incorporated by reference in its entirety.

(15) The present disclosure is not limited to a specific means of forming the compacted particles, and other means of compaction or agglomeration of the perlite fines can be employed additionally or alternatively to compacting rolls. These other means include, for example, tumble/growth agglomeration; low-, medium-, or high pressure agglomeration; punch and die; roller press; high shear mixer granulator; extrusion; and combinations thereof.

(16) Perlite is a generic term for a naturally occurring siliceous rock. One feature which sets perlite apart from other volcanic glasses is that when heated to a suitable point in its softening range, perlite expands from four to twenty times the original volume. This expansion is due, at least in part, to the presence of two to six percent combined water in the crude perlite rock. Firing, i.e., quickly heating to above 1,600° F. (871° C.), causes the crude rock to pop in a manner similar to popcorn yielding a very open, highly porous structure referred to as expanded perlite.

(17) In an embodiment, the amount of expanded perlite fines is about 50 wt % to about 85 wt % of the material, for example about 70 wt % to about 80 wt %, preferably about 75 wt % of the material. In an embodiment, the amount of the water is about 15 wt % to about 25 wt % of the material, for example about 20 wt % of the material.

(18) In an embodiment, the amount of the binder is about 0.25 wt % to about 5.0 wt % of the material, for example about 1.0 wt % to about 4.0 wt %, preferably about 3.0 wt % to about 3.5 wt % of the material. The binder can be starch and/or clay. Preferably, the starch (if any) comprises a cereal starch, for example starch from one or more of rice, millet, wheat, corn or oats. In a preferred embodiment, the starch (if any) comprises pre-gelled cereal starch and can include any waxy or high amylose varieties thereof. The clay can be swelling or non-swelling. Preferably, the clay (if any) comprises one or more clay minerals selected from the group consisting of kaolin, smectite, illite, chlorite, sepiolite, and atapulgite. In a preferred embodiment, the clay (if any) comprises a montmorillonite smectite and most preferably sodium or calcium montmorillonite.

(19) At least a portion of the binder can be added to the expanded perlite fines as a dry mix before the compacting. Alternatively or additionally, at least a portion of the binder can be pre-blended with at least a portion of the water and then added to the expanded perlite fines before the compacting.

(20) In an embodiment, the compacting forms a compacted material such as sheets and/or briquettes of compacted expanded perlite fines. However, the compacted material is not limited to a specific shape, size or form. Furthermore, as noted above, the present disclosure is not limited to a specific means of compaction or agglomeration of the perlite fines to form the compacted material. For example, the compacted material can be in the form of a pellet (e.g., a flattened pellet), a tablet or a puck.

(21) Then the compacted material can be ground and/or crushed, for example by a milling system or any other suitable apparatus known to one skilled in the art, to obtain particles of compacted material comprising expanded perlite. One or more sieves can be used to obtain the particles of compacted material comprising expanded perlite that have a desired size by separating the particles having the desired size from the remainder of the particles. The desired particle size is preferably from about 30 mesh (595 microns) to about 8 mesh (2,380 microns). Preferably, the particles of compacted material comprising expanded perlite are not evenly distributed within the size range. Commercially available shaker screens may be utilized.

(22) The particles of compacted material comprising expanded perlite that have the desired size can be subjected to drying to remove moisture from the particles without substantially damaging the particles. For example, the particles can be transferred to a dryer such as a fluidized bed dryer. The resultant moisture level can be about 0.25% to about 10%, for example about 2%.

(23) The dried particles of compacted material comprising expanded perlite preferably have a density of about 25 lb/ft.³ to about 45 lb/ft.³, more preferably about 30 lb/ft.³ to about 42 lb/ft.³.

(24) In some embodiments, the dried particles of compacted material comprising expanded perlite are combined with a clumping agent; i.e., an agent that binds adjacent particles when wetted. The combination of the dried particles with the clumping agent can be performed in a mixer and can form at least a portion of a clumping pet litter. The clumping litter preferably comprises the dried compacted particles and the clumping agent in a ratio from 99:1 to 94:6, for example about 96:4. Non-limiting examples of suitable clumping agents include bentonite (such as sodium bentonite), guar gum, starches, xanthan gum, gum Arabic, gum acacia, silica gel, other minerals, and mixtures thereof. A preferred embodiment of the clumping agent comprises guar gum. Nevertheless, in an embodiment, starch is used in the binder and additional starch is used in the clumping agent, although the starch used in the binder is added to the expanded perlite fines before and/or during compacting, and the starch used in the clumping agent is added to the particles of compacted perlite, preferably after drying.

- (25) In other embodiments, the dried particles of compacted material comprising expanded perlite are not coated with a clumping agent, and the dried particles of compacted material comprising expanded perlite form at least a portion of a non-clumping litter. In such embodiments, the dried particles can be packaged directly after the drying without further processing.
- (26) Various additives may be optionally applied to the dried compacted particles. Non-limiting examples of suitable additives include an odor control agent, a fragrance, an anti-microbial agent, an anti-sticking agent, an agent for controlling pH, a dye, a coloring agent, a de-dusting agent, a disinfectant, and combinations thereof. In an embodiment, at least a portion of the dried compacted particles are coated with a colorant.
- (27) For embodiments in which the pet litter is a non-clumping litter, the additives can be applied to the dried compacted particles directly after the drying, to form the non-clumping litter, without further processing. Then the non-clumping litter can be packaged directly after the application of the additives, without further processing.
- (28) For embodiments in which the pet litter is a clumping litter, the additives and the clumping agent, together or separately, can be combined with the dried compacted particles directly after the drying, to form the clumping litter, without further processing. Then the clumping litter can be packaged directly after the combination, without further processing.
- (29) In a preferred embodiment, the pet litter does not contain clay. In a preferred embodiment, the pet litter does not contain agricultural products, such as alfalfa, corn, corn stalk, corn flour, oat hull, oat stalk, oat flour, barley hull, barley meal, barley stalk, barley flour, wheat hull, wheat straw, wheat flour, soybean hull, soybean meal, soybean flour, rye hull, rye meal, rye straw, rye flour, rice straw, rice hull, sorghum straw, sorghum hull, sunflower seeds, bamboo, lemongrass, switchgrass, catnip, oregano, parsley, rosemary, sage, thyme, valerian root, alyssum, chrysanthemum, honeysuckle, hops, lavender, apples, berries, orange peels, orange pulp, sunflower hulls, coffee, tea, sawdust, paper, cellulose, corncob, corn kernel, Distillers Dried Grain (DDG), corn pellet, oat pellet, barley pellet, wheat middlings, soybean pellet, rye pellet, rice grain, rice pellet, sorghum grain, sorghum pellet, sunflower seed, almond, pistachio, walnut, pecan, hazelnut, peanut, acorn, wheat middlings, wheat straws, or combinations thereof.
- (30) Another aspect of the present disclosure is a pet litter comprising dried particles of compacted material comprising expanded perlite, the dried particles having a density of about 25 lb/ft.³ to about 45 lb/ft.³, preferably about 30 lb/ft.³ to about 42 lb/ft.³. Yet another aspect of the present disclosure is a pet litter made by any of the methods disclosed herein.
- (31) Another aspect of the present disclosure is a sealed package at least partially enclosing any of the embodiments of the pet litter disclosed herein, for example a sealed box or a sealed bag containing such pet litter. A further aspect of the present disclosure is a method of using a pet litter, the method comprising positioning at least a portion of a pet litter contained by a package into a litter box. The method can manage animal waste, such as cat urine; prevent or treat cat out-of-box elimination; or treat or prevent lower urinary tract diseases in a cat, such as urinary plugs, struvite or oxalite stones, idiopathic cystitis, or renal reflux. In an embodiment, one or more of the pet litters disclosed herein are used to treat a cat having an out-of-box elimination issue. As used herein, a cat that has “an out-of-box elimination issue” is a cat that has eliminated outside of the litter box at least once in the last month, and in an embodiment eliminated outside of the litter box at least once in the last week.

EXAMPLES

(32) The following non-limiting examples are illustrative of embodiments of the pet litters provided by the present disclosure and advantages thereof.

Example 1

Absorbent Granule Production—1

(33) Absorbent granules were produced using a compaction process. 1. Expanded perlite fines, starch, and water were blended and then fed into a set of compacting rolls (Table 1). 2. The

compaction rolls, having roll back-pressure force set-point of 1,300 psi, formed the in-feed into pellets. 3. The pellets were then crushed and sized to -8/+30 mesh. 4. The screened material was then dried to a moisture content of approx. 2%. 5. After drying, the granular absorbent material was evaluated for density, absorption, and particle integrity (attrition).

(34) TABLE-US-00001 TABLE 1 Litter Formulation (pre-dried) Example Example Example Example Ingredient 1 2 3 7 Swelling Clay — — 3.2% — (Bentonite) Non-Swelling Clay — 7.9% — — Perlite Fines 76.3% 69.6% 74.3% 73.3% Starch 3.7% 2.5% 2.5% 3.6% Water 20.0% 20.0% 20.0% 20.0% Guar — — — 3.1%

Example 2

Absorbent Granule Production—2

(35) Absorbent granules were produced using a compaction process. 1. Expanded perlite fines, starch, non-swelling calcium montmorillonite clay, and water were blended and then fed into a set of compacting rolls (Table 1). 2. The compaction rolls, having roll back-pressure force set-point of 1,300 psi, formed the in-feed into pellets. 3. The pellets were then crushed and sized to -8/+30 mesh. 4. The screened material was then dried to a moisture content of approx. 2%. 5. After drying, the granular absorbent material was evaluated for density, absorption, and particle integrity (attrition).

Example 3

Absorbent Granule Production—3

(36) Absorbent granules were produced using a compaction process. 1. Expanded perlite fines, starch, sodium bentonite, and water were blended and then fed into a set of compacting rolls (Table 1). 2. The compaction rolls, having roll back-pressure force set-point of 1,300 psi, formed the in-feed into pellets. 3. The pellets were then crushed and sized to -8/+30 mesh. 4. The screened material was then dried to a moisture content of approx. 2%. 5. After drying, the granular absorbent material was evaluated for density, absorption, and particle integrity (attrition).

Example 4

Bulk Density Measurement

(37) The bulk density of the absorbent granules from Example 1 was measured using a filling hopper (800 284-5779 Seedburo®; part number 151 Filling Hopper complete with 64P Pan), stand, and pint sized (550.06 cm.sup.3 dry volume) sample cup according to the procedure below: 1. The litter was poured into the filling hopper until it was full. 2. Next, the empty pint cup was placed on a balance and the balance was zeroed. 3. The cup was then placed beneath the filling hopper. The distance between the filling hopper discharge, and the top edge of the cup was set at 2 inches. 4. The filling hopper discharge slide was then opened to allow product to fall into the empty sample cup. Litter was allowed to flow until the cup was full, and then for an additional 1 to 2 seconds of overflow. 5. A straight edge was then used to remove excess product from the top of the cup; leveling the cup contents with the rim of the cup. 6. The cup with litter was then returned to the balance and the weight of the litter recorded. 7. Steps 1-6 were repeated three times. 8. Mass value was converted to pounds per cubic foot (lb/ft.sup.3) using the conversion factor 1 gram per cubic centimeter (gm/cm.sup.3) equals 62.4269 lb/ft.sup.3 (1 gram per dry pint (g/dry-pt) equals 0.113358 lb/ft.sup.3).

(38) The average bulk density and standard deviation were calculated and reported in Table 2. As shown in Table 2, the tested pet litter was significantly less dense than the clay litter benchmarks.

Example 5

Absorption by Volume Measurement

(39) The absorption by volume of the litter from Example 1 was measured using a bulk density apparatus (800 284-5779 Seedburo®; part number 151 Filling Hopper complete with 64P Pan); a straight-edge such as a 12 inch ruler; a funnel; a ring support (4") and support stand (24"); a graduated cylinder (at least 250 ml); an interval timer; and a specimen cup with a known volume (150 ml) according to the procedure below. 1. A representative portion of sample was used to fill

about ¾ of the hopper of the bulk density apparatus. 2. A tared specimen cup was placed under the center of the hopper approx. 2¾ inches below the gate opening. The hopper gate was opened quickly and the sample allowed to fill the cup and overflow into the pan below. 3. The sample was leveled to the top edge of the specimen cup using a straight edge and sawing motion. The volume of the sample was now assumed to be equivalent to the volume of the specimen cup. 4. The sample was then transferred to the sorption funnel. The sorption funnel was positioned above the graduated cylinder using the ring support and stand so that the clamped hose end extended ½" to 1" into the cylinder. 5. Using the graduated cylinder as a measure and transfer vessel, 250 ml of cold tap water (V.sub.initial) was added to the sorption funnel. 6. After a 10 minute soak time, the 250 ml graduated cylinder was placed under the funnel drain hose and the hose clamp released. 7. Water from the funnel was allowed to drain into the graduated cylinder for 5 minutes. 8. Using fingers, the hose was squeezed to release any water trapped therein. 9. The graduated cylinder was examined, and the total volume of water drained from the recorded (V.sub.final).

Calculation of Percentage Absorption by Volume:

Volume of water absorbed (ml)=V.sub.initial (initial water volume)–V.sub.final (final water volume) % Absorption by volume=(Volume of water absorbed (ml)/Volume of specimen cup (ml))×100

(40) Average values were recorded and are reported in Table 2. Referring to Table 2, absorption by volume of the tested pet litter is surprisingly greater than that of both the non-clumping clay litter benchmark and intact granules of expanded perlite of the size –8/+30 mesh.

Example 6

Particle Integrity (Attrition) Measurement

(41) The attrition of the absorbent material from Example 1 was measured according to the procedure below: 1: A representative sample of between 150 mL and 300 mL was collected and hand sieved on a 8" diameter 30 mesh sieve. Any particles that passed through were discarded, and any that remained on the screen or stuck in the screen were brushed out and kept for further analysis. 2. The sample was then poured into the bulk density hopper (Seedburo®; part number 151 Filling Hopper) and released into a tared ¼ cup measuring cup (60 mL). A straight edge was used to strike off the excess material from the measuring cup. 3. The tared measuring cup with the material was then placed on the scale to find the original mass of the sample, MO. 4. The weighed sample was poured onto a 40 mesh sieve, and this screen placed on top of a catch pan. The stack was then loaded into a Rotap (RX-29) and shaken with the arm engaged for 4 minutes. 5. After shaking on the Rotap, the material in the pan was discarded, and the material on the screen and the material stuck in the 40 mesh screen were collected and weighed to find the final mass of the sample, MR.

Calculation of Attrition %

Attrition %=((MO–MR)/MO)×100

(42) The results of attrition testing were recorded and are reported in Table 2. Referring to Table 2, the particle integrity of the tested pet litter is good (<1.0%).

Example 7

Clumping Litter Production

(43) The material from Example 1 (using the 500 psi roll back-pressure) was combined with a clumping agent (guar gum). This material was then measured for clumping performance: 1. The litter base material (10 lbs) was added to a lab scale rotational pan mixer (Mars Mineral DP-14). 2. The mixer was set to a low speed setting and guar gum (0.4 lbs) was slowly added. 3. The finished material was then removed from the mixer.

Example 8

Clump Integrity Measurement

(44) The material from Example 7 was tested for clump performance according to the following procedure: 1. An 8" diameter sieve with ¾ mesh was stacked on top of a sieve pan and placed on

the bottom of a support stand. 2. A trap door assembly was attached to the support stand and positioned ten inches above $\frac{3}{4}$ " sieve. 3. A representative sample of the litter from Example 5 was added to a litter testing pan. The depth of material was three inches. 4. A self-leveling 25 ml burette was positioned on a support stand three inches above the litter surface. This setup was used to dispense 25 ml aliquots of feline urine liquid to the litter surface, forming a clump in the litter. This process was repeated in a variety of location of the litter pan until the desired number of clumps was created (in this case 20 clumps). 5. At the end of the desired time interval (15 min or 24 hr), the clump was removed from the litter, and its mass recorded as W1. 6. The clump was then centered on the trap door mechanism assembled in step 2. 7. Next the lever was actuated to release the trap door, allowing the clump to fall onto the $\frac{3}{4}$ " test sieve. 8. The clump was carefully removed from the screen in a manner which allowed loose material to fall free of the clump, but not in a manner which caused additional damage to the clump. If the clump broke into pieces, largest piece retained on the $\frac{3}{4}$ " screen was selected. If nothing is retained on the screen, the result is zero (0) weight. 9. The clump or largest piece was weighed and the mass recorded as W2. 10. The Percentage of Cohesion value was calculated using the following formula:

$$\% \text{ Cohesion} = (W2(\text{final weight}) / W1(\text{initial weight})) \times 100$$

(45) The Percentage of Cohesion values for all clumps were averaged, and the results recorded in Table 2. As shown in Table 2, the Percentage of Cohesion values for the tested pet litter were comparable to that of the current clay litter.

(46) TABLE-US-00002 TABLE 2 Summary of Testing Results Bulk Clump Clump Material
Absorption Density Attrition Cohesion: Cohesion: 24 Class Sample by % Vol (lb/ft.sup.3) (%) 15 min. (%) Hours (%) Raw Material Expanded Perlite 40.6 4.2 2.5 — — Non-swelling (Ca 49.7 46.2 0.19 — — Montmorillonite) Clay Non-clumping Example 1 69.2 33.3 0.96 — — Litter Example 2 66.4 41.2 0.25 — — Example 3 68.4 41.9 0.25 — — Clumping Commercial CL — 55.3 0.19 93.0 98.2 Litter (CL) Example 6 — 33.3 0.96 96.5 97.2

Conclusions

(47) The results show that the tested pet litter is a low density granular absorbent with good particle integrity and has surprisingly improved absorption relative to traditional clay litter and the pre-processed principal raw material. Specifically, the density is reduced relative to both clumping and non-clumping clay litters (Table 2), the particle integrity is good (<1.0%), and the absorption by volume is surprisingly greater than the non-clumping clay litter benchmark as well as intact granules of expanded perlite of the size -8/+30 mesh (Table 2). The tested absorbent material can be used to formulate a clumping pet litter, and demonstrates comparable clumping to that of the clay-based clumping litter benchmark (Table 2).

(48) It should be understood that various changes and modifications to the presently preferred embodiments described herein will be apparent to those skilled in the art. Such changes and modifications can be made without departing from the spirit and scope of the present subject matter and without diminishing its intended advantages. It is therefore intended that such changes and modifications be covered by the appended claims.

Claims

1. A pet litter comprising dried particles of compacted material comprising 50 wt. % to 85 wt. % expanded perlite, wherein the dried particles further comprise a binder comprising starch, wherein the dried particles do not contain a clumping agent and wherein the dried particles have a density of about 25.0 lb/ft.sup.3 to about 45 lb/ft.sup.3.
2. The pet litter of claim 1, wherein the dried particles of compacted material have a moisture content from about 0.25 wt. % to about 10.0 wt %.
3. The pet litter of claim 1, wherein the dried particles of compacted material have a size from 8 (2,380 microns) to 30 mesh (595 microns).

4. The pet litter of claim 1, wherein the dried particles comprise about 1.0 wt. % to about 4.0 wt. % starch.
 5. The pet litter of claim 1, wherein the dried particles have an attrition less than or about 5.0%.
 6. The pet litter of claim 1, further comprising an additive selected from the group consisting of an odor control agent, a fragrance, an anti-microbial agent, an anti-sticking agent, an agent for controlling pH, a dye, a coloring agent, a de-dusting agent, a disinfectant, and combinations thereof.
 7. The pet litter of claim 6, wherein the odor control agent is activated carbon.
 8. The pet litter of claim 1, wherein the starch is a cereal starch.
 9. The pet litter of claim 1, wherein the dried particles of compacted material consist essentially of expanded perlite, starch and water.
 10. A pet litter comprising dried particles of compacted material consisting essentially of expanded perlite and starch, wherein the dried particles have a density of about 25.0 lb/ft.³ to about 45 lb/ft.³.
-