



US012391714B2

(12) **United States Patent**
Kwon et al.(10) **Patent No.:** US 12,391,714 B2
(45) **Date of Patent:** Aug. 19, 2025(54) **ORGANOMETALLIC COMPOUND, ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME, AND DIAGNOSTIC COMPOSITION INCLUDING THE ORGANOMETALLIC COMPOUND**(71) Applicant: **Samsung Electronics Co., Ltd.**, Suwon-si (KR)(72) Inventors: **Ohyun Kwon**, Seoul (KR); **Virendra Kumar Rai**, Hwaseong-si (KR); **Bumwoo Park**, Yongin-si (KR); **Sangdong Kim**, Seongnam-si (KR); **Hyungjun Kim**, Suwon-si (KR); **Myungsun Sim**, Suwon-si (KR); **Byoungki Choi**, Hwaseong-si (KR)(73) Assignee: **SAMSUNG ELECTRONICS CO., LTD.**, Gyeonggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 830 days.

(21) Appl. No.: **17/552,573**(22) Filed: **Dec. 16, 2021**(65) **Prior Publication Data**

US 2022/0185834 A1 Jun. 16, 2022

(30) **Foreign Application Priority Data**

Dec. 16, 2020 (KR) 10-2020-0176596

(51) **Int. Cl.****C07F 15/00** (2006.01)
H10K 85/30 (2023.01)

(Continued)

(52) **U.S. Cl.**
CPC **C07F 15/0033** (2013.01); **H10K 85/342** (2023.02); **H10K 50/11** (2023.02);
(Continued)(58) **Field of Classification Search**
CPC ... C07F 15/0033; C07F 19/00; H10K 85/342;
H10K 85/6572
See application file for complete search history.(56) **References Cited**

U.S. PATENT DOCUMENTS

9,490,437 B2 * 11/2016 Hwang H10K 85/6572
9,522,895 B2 * 12/2016 Boerner C07D 277/66
(Continued)

FOREIGN PATENT DOCUMENTS

CN 1696137 A 11/2005
CN 101679856 A 3/2010
(Continued)

OTHER PUBLICATIONS

Office Action issued Sep. 19, 2024 of KR Patent Application No. 10-2020-0176596.

(Continued)

Primary Examiner — Michael M Dollinger


(74) Attorney, Agent, or Firm — CANTOR COLBURN LLP

(57) **ABSTRACT**


An organometallic compound represented by Formula 1:

$$\text{M}_1(\text{Ln}_1)_{n_1}(\text{Ln}_2)_{n_2}$$
 Formula 1

(Continued)



wherein L_{n_1} is a ligand represented by Formula 1A, L_{n_2} is a ligand represented by Formula 1B, n_1 is 0, 1, or 2, n_2 is 1, 2, or 3, provided that the sum of n_1 and n_2 is at least 3,



wherein CY_1 , CY_2 , CY_3 , R_{10} , R_{20} , R_{30} , X_1 , X_2 , Y_1 to Y_8 , and $b10$ to $b30$ are as described herein, and wherein * and *' each indicate a binding site to M_1 .

20 Claims, 1 Drawing Sheet

- (51) **Int. Cl.**
H10K 50/11 (2023.01)
H10K 101/10 (2023.01)

- H10K 101/30* (2023.01)
H10K 101/40 (2023.01)
(52) **U.S. Cl.**
CPC *H10K 2101/10* (2023.02); *H10K 2101/30* (2023.02); *H10K 2101/40* (2023.02)

(56)

References Cited

U.S. PATENT DOCUMENTS

9,923,154 B2	3/2018	Oshiyama et al.
11,731,994 B2 *	8/2023	Hwang C07F 15/0033 428/690
2010/0127215 A1	5/2010	Boerner et al.
2016/0164012 A1	6/2016	Lee et al.
2017/0012226 A1	1/2017	Hwang et al.
2019/0002629 A1	1/2019	Islam et al.
2019/0252619 A1	8/2019	Tsai et al.
2020/0087334 A1	3/2020	Ji et al.
2020/0181184 A1	6/2020	Hwang et al.
2023/0100639 A1 *	3/2023	Yamada H10K 85/342 257/40


FOREIGN PATENT DOCUMENTS

CN	105461754 A	4/2016
CN	108290915 A	7/2018
CN	110128479 A	8/2019
CN	110903324 A	3/2020
CN	111978355 A	11/2020
JP	2010118381 A	5/2010
JP	2014152151 A	8/2014
JP	2015090939 A	* 5/2015
JP	2016219490 A	12/2016
KR	1020200068447 A	6/2020
WO	2012111548 A1	8/2012
WO	2016056562 A1	4/2016
WO	2017103584 A1	6/2017

OTHER PUBLICATIONS

Extended European Search Report issued dated May 3, 2022 of EP Patent Application No. 21213971.1.
Office Action issued Apr. 24, 2023 of EP Patent Application No. 21213971.1.
Office Action issued Jun. 4, 2025 of CN Patent Application No. 202111534549.5.

* cited by examiner



1

**ORGANOMETALLIC COMPOUND,
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME, AND DIAGNOSTIC
COMPOSITION INCLUDING THE
ORGANOMETALLIC COMPOUND**

CROSS-REFERENCE TO RELATED
APPLICATION

This application claims priority to Korean Patent Application No. 10-2020-0176596, filed on Dec. 16, 2020, in the Korean Intellectual Property Office, and all benefits accruing therefrom under 35 U.S.C. § 119, the content of which is incorporated by reference herein in its entirety.

BACKGROUND

1. Field

One or more embodiments described herein relate to an organometallic compound, an organic light-emitting device including the same, and a diagnostic composition including the organometallic compound.

2. Description of the Related Art

Organic light-emitting devices (OLEDs) are self-emission devices that have improved characteristics compared to conventional devices, including having wider viewing angles, faster response time, excellent brightness, driving voltage, and response speed. In addition, OLEDs can produce full-color images with these enhanced properties.


In an example, an organic light-emitting device includes an anode, a cathode, and an organic layer located between the anode and the cathode, wherein the organic layer includes an emission layer. A hole transport region may be located between the anode and the emission layer, and an electron transport region may be located between the emission layer and the cathode. Holes provided from the anode may move toward the emission layer through the hole transport region, and electrons provided from the cathode may move toward the emission layer through the electron transport region. The holes and the electrons may recombine in the emission layer to produce excitons. These excitons may transition from an excited state to a ground state to thereby generate light, for example, visible light.

SUMMARY

One or more embodiments described herein relate to an organometallic compound, an organic light-emitting device including at least one organometallic compound, and a diagnostic composition including at least one organometallic compound.

Additional aspects will be set forth in part in the detailed description, which follows and, in part, will be apparent from the detailed description, or may be learned by practice of the presented exemplary embodiments of the disclosure.

According to one or more embodiments, an organometallic compound is represented by Formula 1.



Formula 1

In Formula 1,

M_1 is a transition metal,

Ln_1 is a ligand represented by Formula 1A,

Ln_2 is a ligand represented by Formula 1B,


$n1$ is 0, 1, or 2, and

$n2$ is 1, 2, or 3,


60

65

2



Formula 1A



Formula 1B

In Formulae 1A and 1B,

X_1 is C or N, and X_2 is C or N,

Y_1 is $C(R_{41})$ or N, Y_2 is $C(R_{42})$ or N, Y_3 is $C(R_{43})$ or N,

Y_4 is $C(R_{44})$ or N, Y_5 is $C(R_{45})$ or N, Y_6 is $C(R_{46})$ or N,

Y_7 is $C(R_{47})$ or N, Y_8 is $C(R_{48})$ or N,

CY_1 and CY_2 are each independently a C_5 - C_{30} carbocyclic group or a C_1 - C_{30} heterocyclic group,

CY_3 is a C_1 - C_{30} heterocyclic group including nitrogen,

R_{10} , R_{20} , and R_{41} to R_{48} are each independently hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group,

a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_1 - C_{60} alkylthio group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group,

a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_7 - C_{60} alkyl aryl group, a substituted or unsubstituted C_7 - C_{60} aryl alkyl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_2 - C_{60} alkyl heteroaryl group, a substituted or unsubstituted C_2 - C_{60} heteroaryl alkyl group,

a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃),

3

—Ge(Q₁)(Q₂)(Q₃), —N(Q₄)(Q₅), —B(Q₆)(Q₇),
 —P(Q₈)(Q₉), or —P(=O)(Q₈)(Q₉),
 R₃₀ is hydrogen, deuterium, —F, —Cl, —Br, —I, a
 hydroxyl group, a cyano group, a nitro group, an amino
 group, an amidino group, a hydrazine group, a hydra-
 zone group, a carboxylic acid group or a salt thereof, a
 sulfonic acid group or a salt thereof, a phosphoric acid
 group or a salt thereof, a substituted or unsubstituted
 C₂-C₆₀ alkyl group, a substituted or unsubstituted
 C₂-C₆₀ alkenyl group, a substituted or unsubstituted
 C₂-C₆₀ alkynyl group, a substituted or unsubstituted
 C₁-C₆₀ alkoxy group, a substituted or unsubstituted
 C₁-C₆₀ alkylthio group, a substituted or unsubstituted
 C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted
 C₁-C₁₀ heterocycloalkyl group, a substituted or unsub-
 stituted C₃-C₁₀ cycloalkenyl group, a substituted or
 unsubstituted C₂-C₁₀ heterocycloalkenyl group, a sub-
 stituted or unsubstituted C₆-C₆₀ aryl group, a sub-
 stituted or unsubstituted C₇-C₆₀ alkyl aryl group, a sub-
 stituted or unsubstituted C₈-C₆₀ aryl alkyl group, a
 substituted or unsubstituted C₆-C₆₀ aryloxy group, a
 substituted or unsubstituted C₆-C₆₀ arylthio group, a
 substituted or unsubstituted C₁-C₆₀ heteroaryl group, a
 substituted or unsubstituted C₂-C₆₀ alkyl heteroaryl
 group, a substituted or unsubstituted C₃-C₆₀ heteroaryl
 alkyl group, a substituted or unsubstituted C₁-C₆₀ het-
 eroaryloxy group, a substituted or unsubstituted C₁-C₆₀
 heteroarylthio group, a substituted or unsubstituted
 monovalent non-aromatic condensed polycyclic group,
 a substituted or unsubstituted monovalent non-aromatic
 condensed heteropolycyclic group, —Ge(Q₁)(Q₂)(Q₃),
 —N(Q₄)(Q₅), —B(Q₆)(Q₇), —P(Q₈)(Q₉), or —P(=O)
 (Q₈)(Q₉),
 two or more of a plurality of R₁₀(s) are optionally linked
 to each other to form a substituted or unsubstituted
 C₅-C₃₀ carbocyclic group or a substituted or unsubsti-
 tuted C₁-C₃₀ heterocyclic group,
 two or more of a plurality of R₂₀(s) are optionally linked
 to each other to form a substituted or unsubstituted
 C₅-C₃₀ carbocyclic group or a substituted or unsubsti-
 tuted C₁-C₃₀ heterocyclic group,
 two or more of a plurality of R₃₀(s) are optionally linked
 to each other to form a substituted or unsubstituted
 C₅-C₃₀ carbocyclic group or a substituted or unsubsti-
 tuted C₁-C₃₀ heterocyclic group,
 two or more neighboring substituents of R₁₀, R₂₀, R₃₀,
 and R₄₁ to R₄₈ are optionally linked to each other to
 form a substituted or unsubstituted C₅-C₃₀ carbocyclic
 group or a substituted or unsubstituted C₁-C₃₀ hetero-
 cyclic group,
 b10, b20, and b30 are each independently 1, 2, 3, 4, 5, 6,
 7, 8, 9, or 10,
 at least one substituent of the substituted C₅-C₃₀ carbo-
 cyclic group, the substituted C₁-C₃₀ heterocyclic group,
 the substituted C₁-C₆₀ alkyl group, the substituted
 C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkenyl
 group, the substituted C₂-C₆₀ alkynyl group, the sub-
 stituted C₁-C₆₀ alkoxy group, the substituted C₁-C₆₀
 alkylthio group, the substituted C₃-C₁₀ cycloalkyl
 group, the substituted C₁-C₁₀ heterocycloalkyl group,
 the substituted C₃-C₁₀ cycloalkenyl group, the substi-
 tuted C₂-C₁₀ heterocycloalkenyl group, the substituted
 C₆-C₆₀ aryl group, the substituted C₇-C₆₀ alkyl aryl
 group, the substituted C₈-C₆₀ aryl alkyl group, the substi-
 tuted C₇-C₆₀ aryl alkyl group, the substituted C₆-C₆₀
 aryloxy group, the substituted C₆-C₆₀ arylthio
 group, the substituted C₁-C₆₀ heteroaryl group, the

4

substituted C_2 - C_{60} alkyl heteroaryl group, the substituted C_2 - C_{60} heteroaryl alkyl group, the substituted C_3 - C_{60} heteroaryl alkyl group, the substituted C_1 - C_{60} heteroaryloxy group, the substituted C_1 - C_{60} heteroarylthio group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is:
 deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, or a C_1 - C_{60} alkoxy group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryloxy group, a C_1 - C_{60} heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —Ge(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₄)(Q₁₅), —B(Q₁₆)(Q₁₇), —P(Q₈)(Q₉), or —P(=O)(Q₁₈)(Q₁₉), C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryloxy group, a C_1 - C_{60} heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group,
 C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryloxy group, a C_1 - C_{60} heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_1 - C_{60} alkylthio group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_7 - C_{60} alkyl aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a C_2 - C_{60} alkyl heteroaryl group, a C_2 - C_{60} heteroaryl alkyl group, a C_1 - C_{60} heteroaryloxy group, a

$C_1\text{-}C_{60}$ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁) (Q₂₂)(Q₂₃), —Ge(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₄)(Q₂₅), —B(Q₂₆)(Q₂₇), —P(Q₂₈)(Q₂₉), or —P(=O)(Q₂₈) (Q₂₉), or —Si(Q₃₁)(Q₃₂)(Q₃₃), —Ge(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₄) (Q₃₅), —B(Q₃₆)(Q₃₇), —P(Q₂₈)(Q₂₉), or —P(=O) (Q₃₈)(Q₃₉), wherein Q₁ to Q₉, Q₁₁ to Q₁₉, Q₂₁ to Q₂₉, and Q₃₁ to Q₃₉ are each independently hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted $C_1\text{-}C_{60}$ alkyl group, a substituted or unsubstituted $C_2\text{-}C_{60}$ alkenyl group, a substituted or unsubstituted $C_2\text{-}C_{60}$ alkynyl group, a substituted or unsubstituted $C_1\text{-}C_{60}$ alkoxy group, a substituted or unsubstituted $C_1\text{-}C_{60}$ alkylthio group, a substituted or unsubstituted $C_3\text{-}C_{10}$ cycloalkyl group, a substituted or unsubstituted heterocycloalkyl group, a substituted or unsubstituted $C_3\text{-}C_{10}$ cycloalkenyl group, a substituted or unsubstituted $C_2\text{-}C_{10}$ heterocycloalkenyl group, a substituted or unsubstituted $C_6\text{-}C_{60}$ aryl group, a substituted or unsubstituted $C_7\text{-}C_{60}$ alkyl aryl group, a substituted or unsubstituted $C_7\text{-}C_{60}$ aryl alkyl group, a substituted or unsubstituted $C_6\text{-}C_{60}$ aryloxy group, a substituted or unsubstituted $C_6\text{-}C_{60}$ arylthio group, a substituted or unsubstituted $C_1\text{-}C_{60}$ heteroaryl group, a substituted or unsubstituted $C_2\text{-}C_{60}$ heteroaryl group, a substituted or unsubstituted $C_2\text{-}C_{60}$ heteroaryloxy group, a substituted or unsubstituted $C_1\text{-}C_{60}$ heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and

wherein * and ** each indicate a binding site to M₁.

According to one or more embodiments, an organic light-emitting device includes a first electrode, a second electrode, and an organic layer located between the first electrode and the second electrode, wherein the organic layer includes an emission layer, and wherein the organic layer includes at least one of the organometallic compound represented by Formula 1.

According to one or more embodiments, the organometallic compound may be included in the emission layer of the organic layer, and the organometallic compound included in the emission layer may act as a dopant.

According to one or more embodiments, a diagnostic composition includes at least one organometallic compound represented by Formula 1.

BRIEF DESCRIPTION OF THE DRAWING

The above and other aspects, features, and advantages of certain embodiments of the disclosure will be more apparent from the following description taken in conjunction with the accompanying drawing, in which

The FIGURE shows a schematic cross-sectional view of an organic light-emitting device according to one or more embodiments.

DETAILED DESCRIPTION

Reference will now be made in detail to embodiments, examples of which are illustrated in the accompanying

drawings, wherein like reference numerals refer to like elements throughout the specification. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the FIGURES, to explain aspects. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

The terminology used herein is for the purpose of describing one or more exemplary embodiments only and is not intended to be limiting. As used herein, the singular forms “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. The term “or” means “and/or.” It will be further understood that the terms “comprises” and/or “comprising,” or “includes” and/or “including” when used in this specification, specify the presence of stated features, regions, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, regions, integers, steps, operations, elements, components, and/or groups thereof.

It will be understood that, although the terms first, second, third etc. may be used herein to describe various elements, components, regions, layers, and/or sections, these elements, components, regions, layers, and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer, or section from another element, component, region, layer, or section. Thus, a first element, component, region, layer, or section discussed below could be termed a second element, component, region, layer, or section without departing from the teachings of the present embodiments.


Exemplary embodiments are described herein with reference to cross section illustrations that are schematic illustrations of idealized embodiments. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments described herein should not be construed as limited to the particular shapes of regions as illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as flat may, typically, have rough and/or nonlinear features. Moreover, sharp angles that are illustrated may be rounded. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to illustrate the precise shape of a region and are not intended to limit the scope of the present claims.

It will be understood that when an element is referred to as being “on” another element, it can be directly in contact with the other element or intervening elements may be present therebetween. In contrast, when an element is referred to as being “directly on” another element, there are no intervening elements present.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this general inventive concept belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the present disclosure, and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

"About" or "approximately" as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, "about" can mean within one or more standard deviations, or within $\pm 30\%$, 20% , 10% , 5% of the stated value.

According to an aspect of the present disclosure, one or more embodiments describe an organometallic compound represented by Formula 1:



Formula 1

M_1 in Formula 1 is a transition metal.

For example, M_1 may be a Period 1 transition metal, a Period 2 transition metal, or a Period 3 transition metal.

In one or more embodiments, M_1 may be iridium (Ir), platinum (Pt), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), thulium (Tm), or rhodium (Rh).

In one or more embodiments, M_1 may be Ir, Pt, Os, or Rh.

In one or more embodiments, M_1 may be Ir.


In Formula 1, n_1 is 1 or 2, and n_2 may be 1, 2, or 3.

In one or more embodiments, the sum of n_1 and n_2 may be 2 or 3.

In one or more embodiments, M_1 may be Ir and the sum of n_1 and n_2 may be 3.


In one or more embodiments, M_1 may be Pt and the sum of n_1 and n_2 may be 2.

Ln_1 in Formula 1 is a ligand represented by Formula 1A.



Formula 1A

Ln_2 in Formula 1 is a ligand represented by Formula 1B.



Formula 1B

In Formula 1A, X_1 is C or N, and X_2 is C or N.

In Formula 1B, Y_1 is C(R_{41}) or N, Y_2 is C(R_{42}) or N, Y_3 is C(R_{43}) or N, Y_4 is C(R_{44}) or N, Y_5 is C(R_{45}) or N, Y_6 is C(R_{46}) or N, Y_7 is C(R_{47}) or N, and Y_8 is C(R_{48}) or N.

CY_1 and CY_2 in Formula 1A are each independently be a C_5 - C_{30} carbocyclic group or a C_1 - C_{30} heterocyclic group.

CY_3 in Formula 1B is a C_1 - C_{30} heterocyclic group including nitrogen.

5 In one or more embodiments, CY_1 and CY_2 may each independently be i) a first ring, ii) a second ring, iii) a condensed cyclic group in which two or more first rings are condensed with each other, iv) a condensed cyclic group in which two or more second rings are condensed with each other, or v) a condensed cyclic group in which at least one first ring is condensed with at least one second ring,

wherein the first ring may be a cyclopentane group, a cyclopentadiene group, a furan group, a thiophene group, a pyrrole group, a silole group, an indene group, a benzofuran group, a benzothiophene group, an indole group, a benzosilole group, an oxazole group, an isoxazole group, an oxadiazole group, an isoxadiazole group, an oxatriazole group, an isoxatriazole group, a thiazole group, an isothiazole group, a thiadiazole group, an isothiadiazole group, a thiatriazole group, an isothiatriazole group, a pyrazole group, an imidazole group, a triazole group, a tetrazole group, an azasilole group, a diazasilole group, or a triazasilole group, and the second ring may be an adamantane group, a norbornane group, a norbornene group, a cyclohexane group, a cyclohexene group, a phenyl group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, or a triazine group.

10 In one or more embodiments, CY_1 and CY_2 may each independently be a substituted or unsubstituted cyclopentane group, a substituted or unsubstituted cyclohexane group, a substituted or unsubstituted cycloheptane group, a substituted or unsubstituted cyclopentene group, a substituted or unsubstituted cyclohexene group, a substituted or

15 unsubstituted cycloheptene group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthalene group, a substituted or unsubstituted 1,2,3,4-tetrahydronaphthalene group, a substituted or unsubstituted anthracene group, a substituted or unsubstituted phenanthrene group, a substituted or unsubstituted triphenylene group, a substituted or unsubstituted pyrene group,

20 a substituted or unsubstituted chrysene group, a substituted or unsubstituted cyclopentadiene group, a substituted or unsubstituted thiophene group, a substituted or unsubstituted furan group, a substituted or unsubstituted indole group, a substituted or unsubstituted benzoborole group, a substituted or

25 unsubstituted benzophosphole group, a substituted or unsubstituted indene group, a substituted or unsubstituted benzosilole group, a substituted or unsubstituted benzogermole group, a substituted or unsubstituted dibenzoborole group, a substituted or unsub-


30 stituted dibenzophosphole group, a substituted or unsubstituted fluorene group, a substituted or unsubstituted dibenzosilole group, a substituted or unsubstituted dibenzogermole group, a substituted or unsubstituted dibenzothiophene group, substituted or unsubstituted a dibenzo-

35 selenophene group, a substituted or unsubstituted dibenzofuran group, a substituted or unsubstituted dibenzothiophene 5-oxide group, a substituted or unsubstituted 9H-fluoren-9-one group, a substituted or unsubstituted dibenzothiophene 5,5-dioxide group, a substituted or unsubstituted azaindole group, a substituted or unsubstituted azabenzoborole group,

40 a substituted or unsubstituted azabenzophosphole group, a substituted or unsubstituted azaindene group, a substituted or

or unsubstituted azabenzosilole group, a substituted or unsubstituted azabenzogermole group, a substituted or unsubstituted azabenzothiophene group, a substituted or unsubstituted azabenzoselenophene group, a substituted or unsubstituted azabenzo[furan group, a substituted or unsubstituted azacarbazole group, a substituted or unsubstituted azadibenzoborole group, a substituted or unsubstituted azadibenzophosphole group, a substituted or unsubstituted azafluorene group, a substituted or unsubstituted azadibenzo[silole group, a substituted or unsubstituted azadibenzo[germole group, a substituted or unsubstituted azadibenzo[thiophene group, a substituted or unsubstituted azadibenzo[selenophene group, a substituted or unsubstituted azadibenzo[furan group, a substituted or unsubstituted azadibenzo[thiophene 5-oxide group, a substituted or unsubstituted aza-9H-fluoren-9-one group, a substituted or unsubstituted azadibenzo[thiophene 5,5-dioxide group, a substituted or unsubstituted pyridine group, a substituted or unsubstituted pyrimidine group, a substituted or unsubstituted pyrazine group, a substituted or unsubstituted pyridazine group, a substituted or unsubstituted triazine group, a substituted or unsubstituted quinoline group, a substituted or unsubstituted isoquinoline group, a substituted or unsubstituted quinoxaline group, a substituted or unsubstituted quinazoline group, a substituted or unsubstituted phenanthroline group, a substituted or unsubstituted pyrrole group, a substituted or unsubstituted pyrazole group, a substituted or unsubstituted imidazole group, a substituted or unsubstituted triazole group, a substituted or unsubstituted oxazole group, a substituted or unsubstituted isoxazole group, a substituted or unsubstituted thiazole group, a substituted or unsubstituted isothiazole group, a substituted or unsubstituted oxadiazole group, a substituted or unsubstituted thiadiazole group, a substituted or unsubstituted benzopyrazole group, a substituted or unsubstituted benzimidazole group, a substituted or unsubstituted benzoxazole group, a substituted or unsubstituted benzothiazole group, a substituted or unsubstituted benzoxadiazole group, a substituted or unsubstituted benzothiadiazole group, a substituted or unsubstituted 5,6,7,8-tetrahydroisoquinoline group, or a substituted or unsubstituted 5,6,7,8-tetrahydroquinoline group; or

a group represented by Formulae 8-1 or 8-2:



Formula 8-1

Formula 8-2

In Formulae 8-1 and 8-2,

Y_{81} to Y_{84} may each independently be a single bond, O, S, N(R_{81}), C(R_{81}) (R_{82}) , Si(R_{81}) (R_{82}) , C(=O), S(=O), S(=O)₂, B(R_{81}), P(R_{81}), or P(=O)(R_{81}),

CY₈₁ to CY₈₃ may each independently be a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthalene group, a substituted or unsubstituted 1,2,3,4-tetrahydronaphthalene group, a substituted or unsubstituted phenanthrene group, a substituted or unsubstituted pyridine group, a substituted or unsub-

stituted pyrimidine group, a substituted or unsubstituted pyrazine group, a substituted or unsubstituted triazine group, a substituted or unsubstituted quinoline group, a substituted or unsubstituted isoquinoline group, a substituted or unsubstituted quinoxaline group, a substituted or unsubstituted quinazoline group, a substituted or unsubstituted phenanthroline group, a substituted or unsubstituted benzofuran group, a substituted or unsubstituted benzothiophene group, a substituted or unsubstituted fluorene group, a substituted or unsubstituted carbazole group, a substituted or unsubstituted dibenzofuran group, a substituted or unsubstituted dibenzothiophene group, a substituted or unsubstituted dibenzosilole group, a substituted or unsubstituted azafluorene group, a substituted or unsubstituted azacarbazole group, a substituted or unsubstituted azadibenzofuran group, a substituted or unsubstituted azadibenzothiophene group, or a substituted or unsubstituted azadibenzosilole group.

R_{81} and R_{82} may each independently be as described in connection with R_{10} and R_{20} .

In one or more embodiments, in Formulae 8-1 and 8-2, Y₈₁ to Y₈₄ may each independently be a single bond, O, S, N(R₈₁), C(R₈₁)(R₈₂), or Si(R₈₁)(R₈₂).

In one or more embodiments, Y_{81} and Y_{82} may not be a single bond at the same time, and Y_{83} and Y_{84} may not be a single bond at the same time. For example, in one or more embodiments, Y_{81} and Y_{82} are not both a single bond, and Y_{83} and Y_{84} are not both a single bond.

In one or more embodiments, CY₈₁ to CY₈₃ may be each independently a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthalene group, a substituted or unsubstituted pyridine group, or a substituted or unsubstituted pyrimidine group.

In one or more embodiments, CY₈₁ to CY₈₃ may each independently be a substituted or unsubstituted phenyl group or a substituted or unsubstituted naphthalene group.

45 substituted or unsubstituted pyridine group, a substituted or unsubstituted pyrimidine group, a substituted or unsubstituted pyrazine group, a substituted or unsubstituted triazine group, a substituted or unsubstituted quinoline group, a substituted or unsubstituted isoquinoline group, a substituted or unsubstituted quinoxaline group, a substituted or unsub-

or unsubstituted quinoxaline group, a substituted or unsubstituted quinazoline group, a substituted or unsubstituted phenanthroline group, a substituted or unsubstituted benzofuran group, a substituted or unsubstituted benzothiophene group, a substituted or unsubstituted fluorene group, a

substituted or unsubstituted carbazole group, a substituted or
55 unsubstituted dibenzofuran group, a substituted or unsub-
stituted dibenzothiophene group, a substituted or unsubsti-
tuted dibenzosilole group, a substituted or unsubstituted
azafluorene group, a substituted or unsubstituted azacarba-
zole group, a substituted or unsubstituted azadibenzofuran
60 group, a substituted or unsubstituted azadibenzothiophene
group, or a substituted or unsubstituted azadibenzosilole
group.

In one or more embodiments, CY₁ may be a substituted or unsubstituted pyridine group, a substituted or unsubstituted 65 pyrimidine group, a substituted or unsubstituted pyrazine group, a substituted or unsubstituted triazine group, a substituted or unsubstituted quinoline group, a substituted or

11

unsubstituted isoquinoline group, a substituted or unsubstituted quinoxaline group, or a substituted or unsubstituted quinazoline group.

In one or more embodiments, CY₂ may be a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthalene group, a substituted or unsubstituted pyridine group, a substituted or unsubstituted pyrimidine group, a substituted or unsubstituted pyrazine group, a substituted or unsubstituted triazine group, a substituted or unsubstituted quinoline group, a substituted or unsubstituted isoquinoline group, a substituted or unsubstituted quinoxaline group, a substituted or unsubstituted quinazoline group, a substituted or unsubstituted fluorene group, a substituted or unsubstituted carbazole group, a substituted or unsubstituted dibenzofuran group, a substituted or unsubstituted dibenzothiophene group, or substituted or unsubstituted a dibenzosilole group.

In one or more embodiments, CY₃ may be a substituted or unsubstituted pyridine group, a substituted or unsubstituted pyrimidine group, a substituted or unsubstituted pyrazine group, a substituted or unsubstituted triazine group, a substituted or unsubstituted quinoline group, a substituted or unsubstituted isoquinoline group, a substituted or unsubstituted quinoxaline group, or a substituted or unsubstituted quinazoline group.

R₁₀, R₂₀, and R₄₁ to R₄₈ in Formula 1 are each independently hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₁-C₆₀ alkylthio group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₆₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₇-C₆₀ alkyl aryl group, a substituted or unsubstituted C₇-C₆₀ aryl alkyl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted C₂-C₆₀ alkyl heteroaryl group, a substituted or unsubstituted C₂-C₆₀ heteroaryl alkyl group, a substituted or unsubstituted C₁-C₆₀ heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), —Ge(Q₃)(Q₄)(Q₅), —B(Q₆)(Q₇), —P(Q₈)(Q₉), or —P(=O)(Q₈)(Q₉).

b10, b20, and b30 in Formulae 1A and 1B are each independently 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10.

In one or more embodiments, b10, b20, and b30 may each independently be 1, 2, 3, 4, 5, 6, 7, or 8.

In one or more embodiments, b10, b20, and b30 may each independently be 1, 2, 3, or 4.

In one or more embodiments, b10, b20, and b30 may each independently be 1 or 2.

In one or more embodiments, b10, b20, and b30 may each independently be 1.

12

In one or more embodiments, R₁₀, R₂₀, and R₄₁ to R₄₈ may each independently be:

hydrogen, deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, —SF₅, a C₁-C₂₀ alkyl group, or a C₁-C₂₀ alkoxy group;

a C₁-C₂₀ alkyl group or a C₁-C₂₀ alkoxy group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, a pyridinyl group, or a pyrimidinyl group;


a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysanyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoaxazolyl group, an isobenzoaxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysanyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group,

13

a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group; or —Si(Q₁)(Q₂)(Q₃), —Ge(Q₁)(Q₂)(Q₃), —N(Q₄)(Q₅), —B(Q₆)(Q₇), —P(Q₈)(Q₉), or —P(=O)(Q₈)(Q₉).


In one or more embodiments, R₁₀, R₂₀, and R₄₁ to R₄₈ may each independently be:
hydrogen, deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, —Si(Q₃)(Q₄)(Q₅), or —Ge(Q₃)(Q₄)(Q₅); or
a group represented by one of Formulae 9-1 to 9-61, 9-201 to 9-237, 10-1 to 10-141, or 10-201 to 10-350:



55
60
65

14
-continued


9-6




65

US 12,391,714 B2

15
-continued




16
-continued




US 12,391,714 B2

17
-continued




18
-continued




US 12,391,714 B2

19
-continued




20
-continued




US 12,391,714 B2

21
-continued













22
-continued




US 12,391,714 B2

23
-continued




24
-continued


10-22




10-23 10




15




10-24



20




10-25




25


10-26 30



30




10-27 35




35

10-28




40




45

10-29




50

10-30




55

10-31 60



60



65

10-32

10-33

10-34

10-35

10-36

10-37

10-38


10-39

10-40


10-41

10-42


25
-continued




26
-continued




27




28
-continued



29
-continued




30
-continued




US 12,391,714 B2

31
-continued




32




US 12,391,714 B2

33
-continued











34
-continued




US 12,391,714 B2

35
-continued




36
-continued

10-124 10-132




5




10

10-125 10-133 10-134




15

10-126 10-135 10-136




20



25


10-127 10-137 10-138



35


40

10-128 10-139 10-140



45


10-129 10-139 10-140



50


55

10-130 10-140 10-141



60


10-131 10-141




65

US 12,391,714 B2

37
-continued




38
-continued




US 12,391,714 B2

39
-continued




40
-continued




US 12,391,714 B2

41
-continued




42
-continued




43

-continued










**44**

-continued




US 12,391,714 B2

45
-continued




46
-continued

10-271




5

10-272




15

10-273




20

10-274




25

10-275




30

10-276 40




45

10-277




50

10-278



55

10-279 60



65

10-280

10-281

10-282

10-283

10-284

10-285

10-286

10-287

10-288


10-289

10-290


10-291

US 12,391,714 B2

47









48
-continued



US 12,391,714 B2


49
-continued



50


-continued

10-313




5

10-314




10

10-315




15

10-316




20

10-317



25

10-318




30

45

55

10-319



60

65

10-320

10-321

10-322

10-323







10-324

10-325

10-326


US 12,391,714 B2

51
-continued




52
-continued

10-327




5

10-328




15

10-329




20

10-330




30

10-331




40

10-332




45

10-333



50

60



65

10-334

10-335

10-336

10-337

10-338

10-339









10-340

10-341

10-342

53

-continued



In Formulae 9-1 to 9-61, 9-201 to 9-237, 10-1 to 10-141, and 10-201 to 10-350,

* indicates a binding site to a neighboring atom,

Ph is a phenyl group,

TMS is a trimethylsilyl group,

TMG is a trimethylgermyl group,

g_5 may be an integer from 1 to 5,

g_{10} may be an integer from 1 to 10, and

g_{11} may be an integer from 2 to 11.

R_{30} in Formula 1B is hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted $C_1\text{-}C_{60}$ alkyl group, a substituted or unsubstituted $C_2\text{-}C_{60}$ alkenyl group, a substituted or unsubstituted $C_2\text{-}C_{60}$ alkynyl group,

54

10-343 5 a substituted or unsubstituted $C_1\text{-}C_{60}$ alkoxy group, a substituted or unsubstituted $C_1\text{-}C_{60}$ alkylthio group, a substituted or unsubstituted $C_3\text{-}C_{10}$ cycloalkyl group, a substituted or unsubstituted heterocycloalkyl group, a substituted or unsubstituted $C_3\text{-}C_{10}$ cycloalkenyl group, a substituted or unsubstituted $C_2\text{-}C_{10}$ heterocycloalkenyl group, a substituted or unsubstituted $C_6\text{-}C_{60}$ aryl group, a substituted or unsubstituted $C_7\text{-}C_{60}$ alkyl aryl group, a substituted or unsubstituted $C_7\text{-}C_{60}$ aryl alkyl group, a substituted or unsubstituted $C_6\text{-}C_{60}$ aryloxy group, a substituted or unsubstituted $C_6\text{-}C_{60}$ arylthio group, a substituted or unsubstituted $C_1\text{-}C_{60}$ heteroaryl group, a substituted or unsubstituted $C_2\text{-}C_{60}$ alkyl heteroaryl group, a substituted or unsubstituted $C_2\text{-}C_{60}$ heteroaryl alkyl group, a substituted or unsubstituted $C_1\text{-}C_{60}$ heteroaryloxy group, a substituted or unsubstituted $C_1\text{-}C_{60}$ heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Ge(Q_1)(Q_2)(Q_3), —N(Q_4)(Q_5), —B(Q_6)(Q_7), —P(Q_8)(Q_9), or —P(=O)(Q_8)(Q_9).

In one or more embodiments, R_{30} may be:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, —SF₅, a $C_1\text{-}C_{20}$ alkyl group, a $C_1\text{-}C_{20}$ alkoxy group, or a $C_1\text{-}C_{20}$ alkylthio group;

a $C_2\text{-}C_{20}$ alkyl group or a $C_1\text{-}C_{20}$ alkoxy group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a $C_1\text{-}C_{10}$ alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, a pyridinyl group, or a pyrimidinyl group;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysanyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzo-

thiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group; a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a C₁-C₂₀ alkylthio group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group; or
—Ge(Q₁)(Q₂)(Q₃), —N(Q₄)(Q₅), —B(Q₆)(Q₇), —P(Q₈)(Q₉), or —P(=O)(Q₅)(Q₆).

In one or more embodiments, R₃₀ may be: hydrogen, deuterium, —F, —Cl, —Br, —I, a C₂-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, or —Ge(Q₁)(Q₂)(Q₃), or

a group represented by one of Formulae 9-1 to 9-61, 9-201 to 9-237, 10-1 to 10-141, or 10-201 to 10-350.

In one or more embodiments, R_{30} may be:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, —SF₅, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, or a C₁-C₂₀ alkylthio group;

a C₂-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, or a C₁-C₂₀ alkylthio group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, a pyridinyl group, or a pyrimidinyl group;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysanyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cydoheptenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysanyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group,

a benzothiophenyl group, a benzoisothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group, each substituted with one or more of —F, —Cl, —Br, —I, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a C₁-C₂₀ alkylthio group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysene group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group; or

—Ge(Q₁)(Q₂)(Q₃), —N(Q₄)(Q₅), —B(Q₆)(Q₇), —P(Q₈) (Q₉), or —P(=O)(Q₈)(Q₉).

In one or more embodiments, R₃₀ may be:

hydrogen, —F, —Cl, —Br, —I, a C₂-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group substituted with deuterium, a C₂-C₆₀ alkynyl group, a C₁-C₂₀ alkoxy group, a C₁-C₂₀ alkylthio group, or —Ge(Q₁)(Q₂)(Q₃), or a group represented by one of Formulae 9-1 to 9-61, 9-201 to 9-237, 10-1 to 10-141, or 10-201 to 10-350 as described herein.

In one or more embodiments, R₃₀ may be hydrogen, a C₂-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group substituted with deuterium, or —Ge(Q₁)(Q₂)(Q₃).

Q₁ to Q₉, Q₁₁ to Q₁₉, Q₂₁ to Q₂₉, and Q₃₁ to Q₃₉ are each independently hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₁-C₆₀ alkylthio group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubsti-

tuted C₆-C₆₀ aryl group, a substituted or unsubstituted C₇-C₆₀ alkyl aryl group, a substituted or unsubstituted C₇-C₆₀ aryl alkyl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted C₂-C₆₀ heteroaryl group, a substituted or unsubstituted C₂-C₆₀ heteroaryl alkyl group, a substituted or unsubstituted C₁-C₆₀ heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

In one or more embodiments, Q₁ to Q₉, Q₁₁ to Q₁₉, Q₂₁ to Q₂₉, and Q₃₁ to Q₃₉ may each independently be:

—CH₃, —CD₃, —CD₂H, —CDH₂, —CH₂CH₃, —CH₂CD₃, —CH₂CD₂H, —CH₂CDH₂, —CHDCH₃, —CHDCD₂H, —CHDCDH₂, —CHDCD₃, —CD₂CD₃, —CD₂CD₂H, or —CD₂CDH₂,


an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, a phenyl group, or a naphthyl group; or

an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, a phenyl group, or a naphthyl group, each substituted with one or more of deuterium, a C₁-C₁₀ alkyl group, or a phenyl group.

Two or more of a plurality of R₁₀(s) are optionally linked to each other to form a substituted or unsubstituted C₅-C₃₀ carbocyclic group or a substituted or unsubstituted C₁-C₃₀ heterocyclic group; two or more of a plurality of R₂₀(s) are optionally linked to each other to form a substituted or unsubstituted C₅-C₃₀ carbocyclic group or a substituted or unsubstituted C₁-C₃₀ heterocyclic group; two or more of a plurality of R₃₀(s) are optionally linked to each other to form a substituted or unsubstituted C₅-C₃₀ carbocyclic group or a substituted or unsubstituted C₁-C₃₀ heterocyclic group; and two or more neighboring substituents of R₁₀, R₂₀, R₃₀, and R₄₁ to R₄₈ are optionally linked to each other to form a substituted or unsubstituted C₅-C₃₀ carbocyclic group or a substituted or unsubstituted C₁-C₃₀ heterocyclic group.


In one or more embodiments, two or more of a plurality of R₁₀(s), two or more of a plurality of R₂₀(s); and/or two or more neighboring substituents of Ar₁, R₁, R₂, R₁₀, R₂₀, and R₄₁ to R₄₈ may optionally be linked to each other via a single bond, a double bond or first linking group to form a C₅-C₃₀ carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C₁-C₃₀ heterocyclic group unsubstituted or substituted with at least one R_{10a}. (for example, a fluorene group, a xanthene group, an acridine group, etc.) unsubstituted or substituted with at least one R_{10a}. R_{10a} is as described in connection with R₁₀.

In one or more embodiments, CY₁ in Formula 1A may be represented by one of Formulae 1-1 to 1-16:




US 12,391,714 B2


59
-continued



60
-continued



61
-continued



In Formulae 1-1 to 1-16,

X₁₁ may be O, S, N(R_{19a}), C(R_{19a})(R_{19b}), or Si(R_{19a})₂ 25

R₁₁ to R₁₈, R_{19a}, and R_{19b} are each independently as described in connection with R₁₀,

two or more neighboring substituents of R₁₁ to R₁₈, R_{19a}, and R_{19b} may optionally be linked to each other to form a substituted or unsubstituted C₅-C₃₀ carbocyclic group or a substituted or unsubstituted C₁-C₃₀ heterocyclic group,

wherein, when R₁₁ to R₁₈, R_{19a}, or R_{19b} is —Si(Q₁)(Q₂)(Q₃) or —Ge(Q₁)(Q₂)(Q₃), Q₁ to Q₃ may each independently be:

—CH₃, —CD₃, —CD₂H, —CDH₂, —CH₂CH₃, —CH₂CD₃, —CH₂CD₂H, —CH₂CDH₂, —CHDCH₃, —CHDCD₂H, —CHDCDH₂, —CHDCD₃, —CD₂CD₃, —CD₂CD₂H, or —CD₂CDH₂; 40


an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, a phenyl group, or a naphthyl group; or

an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, a phenyl group, or a naphthyl group, each substituted with one or more of deuterium, a C₁-C₁₀ alkyl group, or a phenyl group, 50

* indicates a binding site to M₁, and


' indicates a binding site to ring CY₂.

In one or more embodiments, CY₂ in Formula 1A may be 55 represented by one of Formulae 2-1 to 2-22:




62
-continued


1-15




10




15




20



25




45



50

2-1



60

2-2

2-3

2-4

2-5


2-6

2-7


2-8

US 12,391,714 B2

63
-continued




64



65

-continued




In Formulae 2-1 to 2-22,
 X_{21} and X_{22} may each independently be O, S, N(R_{29a}), 40
 $C(R_{29a})(R_{29b})$, or Si($R_{29a})(R_{29b})$,
 R_{21} to R_{28} , R_{29a} , and R_{29b} are each independently as
described in connection with R_{20} , and
two or more neighboring substituents of R_{21} to R_{28} , R_{29a} ,
and R_{29b} may optionally be linked to each other to form
a substituted or unsubstituted C_5 - C_{30} carbocyclic group
or a substituted or unsubstituted C_1 - C_{30} heterocyclic
group,
wherein, when R_{21} to R_{28} , R_{29a} , or R_{29b} is —Si($Q_1)(Q_2)$
(Q_3) or —Ge($Q_1)(Q_2)(Q_3$), Q_1 to Q_3 may each inde- 50
pendently be:
—CH₃, —CD₃, —CD₂H, —CDH₂, —CH₂CH₃,
—CH₂CD₃, —CH₂CD₂H, —CH₂CDH₂, —CHDCH₃,
—CHDCD₂H, —CHDCDH₂, —CHDCD₃,
—CD₂CD₃, —CD₂CD₂H, or —CD₂CDH₂,
an n-propyl group, an isopropyl group, an n-butyl group, 55
an isobutyl group, a sec-butyl group, a tert-butyl group,
an n-pentyl group, an isopentyl group, a sec-pentyl
group, a tert-pentyl group, a phenyl group, or a naph-
thyl group; or
an n-propyl group, an isopropyl group, an n-butyl group, 60
an isobutyl group, a sec-butyl group, a tert-butyl group,
an n-pentyl group, an isopentyl group, a sec-pentyl
group, a tert-pentyl group, a phenyl group, or a naph-
thyl group, each substituted with one or more of
deuterium, a C_1 - C_{10} alkyl group, or a phenyl group, 65
* indicates a binding site to ring CY₁, and
** indicates a binding site to M₁.

66

In one or more embodiments, two or more neighboring substituents of R_{11} to R_{18} , R_{19a} , and R_{19b} , or R_{21} to R_{28} , R_{29a} , and R_{29b} may be optionally linked to each other to form a C_5 - C_{30} carbocyclic group unsubstituted or substituted with at least one R_{10a} ; or a C_1 - C_{30} heterocyclic group unsubstituted or substituted with at least one R_{10a} .










For example, two or more neighboring substituents of R_{11} to R_{18} , R_{19a} , or R_{19b} , or R_{21} to R_{28} , R_{29a} , or R_{29b} may 10
optionally be linked to each other to form a cyclopentane
group, a cyclopentene group, a cyclopentadiene group, a
furan group, a thiophene group, a pyrrole group, a silole
group, an adamantane group, a norbornane group, a nor-
bornene group, a cyclohexane group, a cyclohexene group,
15 a phenyl group, a naphthalene group, an indene group, an
indole group, a benzofuran group, a benzothiophene group,
a benzsilole group, a fluorene group, a carbazole group, a
dibenzofuran group, a dibenzothiophene group, or dibenzo-
silole group, each unsubstituted or substituted with at least
20 one R_{10a} .

In one or more embodiments, CY₃ in Formula 1B may be represented by one of Formulae 3-1 to 3-16:




67

-continued

**68**


-continued

3-7



5

3-8



10

3-9

15

In Formulae 3-1 to 3-16,

R₃₁ to R₃₄ may each independently be as described in connection with R₃₀,* indicates a binding site to M₁, and


* indicates a binding site to a neighboring atom.

In one or more embodiments, the organometallic compound may be a compound represented by Formula 11-1:

20

Formula 11-1

3-10



25

3-11

30

35

3-12

In Formula 11-1,

M₁, n1, n2, CY₁, CY₂, Y₁ to Y₈, R₁₀, R₂₀, b10 and b20 each are as described herein,X₃₁ may be C(R₃₁) or N, X₃₂ may be C(R₃₂) or N, X₃₃ may be C(R₃₃) or N, and X₃₄ may be C(R₃₄) or N, R₃₁ to R₃₄ are each independently as described in connection with R₃₀, and

3-13

45

two or more of R₃₁ to R₃₄ may optionally be linked to form a substituted or unsubstituted C₅-C₃₀ carbocyclic group or a substituted or unsubstituted C₁-C₃₀ heterocyclic group.

In one or more embodiments, two or more neighboring

50 substituents of R₃₁ to R₃₄ are optionally linked to form a C₅-C₃₀ carbocyclic group unsubstituted or substituted with at least one R_{10a}, or a C₁-C₃₀ heterocyclic group unsubstituted or substituted with at least one R_{10a}.

3-14


For example, two or more neighboring substituents of R₃₁ to R₃₄ may optionally be linked to each other to form a cyclopentane group, a cyclopentene group, a cyclopentadiene group, a furan group, a thiophene group, a pyrrole group, a silole group, an adamantane group, a norbornane group, a norbornene group, a cyclohexane group, a cyclohexene group, a phenyl group, a naphthalene group, an indene group, an indole group, a benzofuran group, a benzothiophene group, a benzosilole group, a fluorene group, a carbazole group, a dibenzofuran group, a dibenzothiophene group, or dibenzosilole group, each unsubstituted or substituted with at least one R_{10a}.

3-15

In one or more embodiments, examples of the "C₅-C₃₀ carbocyclic group unsubstituted or substituted with at least

one R_{10a}, or a C₁-C₃₀ heterocyclic group unsubstituted or substituted with at least one R_{10a}" include a phenyl group, a naphthalene group, a cyclopentane group, a cyclopentene group, a cyclopentadiene group, a cyclohexane group, a cyclohexene group, a cycloheptane group, a cycloheptene group, a bicyclo[2.2.1]heptane group, a furan group, a thiophene group, a pyrrole group, a silole group, an indene group, a benzofuran group, a benzothiophene group, an indole group, or a benzisole group, each unsubstituted or substituted with at least one R_{10a}. R_{10a} may be as described in connection with R₁₀. The C₅-C₃₀ carbocyclic group and the C₁-C₃₀ heterocyclic group each may be as described herein.

In one or more embodiments, the organometallic compound may be a compound represented by Formula 12-1:



In Formula 12-1,
M₁, n₁, n₂, CY₁, CY₂, R₁₀, R₂₀, b₁₀, b₂₀, and R₄₁ to R₄₈
each may be as described herein, and
R₃₁ to R₃₄ each may be independently as described in
connection with R₃₀.

In one or more embodiments, at least one of R_{10(s)} in the number of b₁₀, R_{20(s)} in the number of b₂₀, and R_{30(s)} in the number of b₃₀ may be a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, —Si(Q₁)(Q₂)(Q₃), or —Ge(Q₁)(Q₂)(Q₃).

In one or more embodiments, at least one of R_{10(s)} in the number of b₁₀, R_{20(s)} in the number of b₂₀, and R_{30(s)} in the number of b₃₀ may be a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a 2-methylbutyl group, a sec-pentyl group, a tert-pentyl group, a neo-pentyl group, a 3-pentyl group, a 3-methyl-2-butyl group, a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, a phenyl group, a biphenyl group, a C₁-C₂₀alkyl phenyl group, a naphthyl group, —Si(Q₁)(Q₂)(Q₃), or —Ge(Q₁)(Q₂)(Q₃).

In one or more embodiments, at least one of R₃₁ to R₃₄ in Formula 11-1 or Formula 12-1 may be a substituted or unsubstituted C₂-C₆₀ alkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, or —Ge(Q₁)(Q₂)(Q₃).

In one or more embodiments, at least one of R₃₁ to R₃₄ in Formula 11-1 or Formula 12-1 may be a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a n-pentyl group, an isopentyl group, a 2-methylbutyl group, a sec-pentyl group, a tert-pentyl group, a neo-pentyl group, a 3-pentyl group, a 3-methyl-2-butyl group, a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, a phenyl group, a biphenyl group, a C₁-C₂₀alkyl phenyl group, a naphthyl group, —Si(Q₁)(Q₂)(Q₃), or —Ge(Q₁)(Q₂)(Q₃).



tert-butyl group, an n-pentyl group, an isopentyl group, a 2-methylbutyl group, a sec-pentyl group, a tert-pentyl group, a neo-pentyl group, a 3-pentyl group, a 3-methyl-2-butyl group, —CH₂CD₃, —CH₂CD₂H, —CH₂CDH₂, —CHDCH₃, —CHDCD₂H, —CHDCDH₂, —CHDCD₃, —CD₂CD₃, —CD₂CD₂H, —CD₂CDH₂, a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, a phenyl group, a biphenyl group, a C₁-C₂₀ alkyl phenyl group, a naphthyl group, —Si(Q₁)(Q₂)(Q₃), or —Ge(Q₁)(Q₂)(Q₃).

In one or more embodiments, at least one of R₃₁ to R₃₄ in Formulae 3-1 to 3-16 may be a substituted or unsubstituted C₂-C₆₀ alkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, or —Ge(Q₁)(Q₂)(Q₃).





In one or more embodiments, at least one of R₃₁ to R₃₄ in Formulae 3-1 to 3-16 may be an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a 2-methylbutyl group, a sec-pentyl group, a tert-pentyl group, a neo-pentyl group, a 3-pentyl group, a 3-methyl-2-butyl group, —CH₂CD₃, —CH₂CD₂H, —CH₂CDH₂, —CHDCH₃, —CHDCD₂H, —CHDCDH₂, —CHDCD₃, —CD₂CD₃, —CD₂CD₂H, —CD₂CDH₂, a phenyl group, a biphenyl group, a C₁-C₂₀ alkyl phenyl group, a naphthyl group, or —Ge(Q₁)(Q₂)(Q₃).

In one or more embodiments, the organometallic compound may be electrically neutral.





In one or more embodiments, the organometallic compound may be one of Compounds 1 to 179:



71
-continued



72
-continued







7

9


10

73
-continued



74
-continued

11




5

10

15

12



20

25

30

16


13

35

40

45

17




14

50


55

60


18




65

75
-continued

19




20



21

35




22

50


55

60


65

76
-continued


23



24




25




26


77
-continued



27
5
10
15
20




25
30
35
40




29
50
55
60
65


78
-continued



30




31



32

79
-continued



33


5

10

15

20

80
-continued



36

25



34

30


35

40

37



45



35


50

55


60

65


38




81
-continued




39



10




15




20


82
-continued




5



25



30



35





43

44

45





46

83
-continued











84
-continued

47 5 10 15 20 25 30 35 40 45 50 55 60 65 51 52 53 54




85








-continued



87
-continued




88
-continued




89


-continued



71




72



73

90

-continued




5

10

15

74




20

25

27

75




35

40

45

76



50

55


60

77

65

91
-continued

78



5

10

15

79

20

25

30

80

35

40

50

81


55

60


65

92
-continued


82




83




84



85



93
-continued



86


5

10


15

20

94
-continued



89



87


30

35

40

45

90



88


50


55

60

65

91



95
-continued


92

5


10

15

20

96
-continued

95



93



30

35

40

45

96




94

55


60

65

97




97
-continued




98

98
-continued




20

101




99
25

102




40

45



100
50


103




55

60


65

99
-continued


104

100
-continued


107




105 25



108




106



109

101
-continued



110

5

10

15

20

25

30

35

40

45


50

55


60

65


102
-continued




113





114



115







116




103

-continued

**104**

-continued

117



5

10

15

20

25

30

35

40

45


50

55


60

65


121




118




122



123




124




105


-continued




125



126




127



128

106

-continued



5

10

15

20

129

25

30

35

130

40


45

50

55







60

65





131

107
-continued



35



50


55

60



65

109




-continued

**110**

-continued




35




111
-continued


148




149



150 35




151




112
-continued


152




153



154




155



113
-continued


156



20


114
-continued

159




25

157




40




45

158



60




55



65


161

115
-continued




116
-continued


162 165




20 166




40 45 167




117
-continued



168




169




118
-continued


171



172



45



173

170

50


55

60


65

119


-continued



174




175




176

120


-continued



20



35



45

55 The organometallic compound represented by Formula 1 satisfies the structure of Formula 1 and includes at least one bidentate ligand represented by Formula 1B. In one or more embodiments, among the bidentate ligands represented by Formula 1B, a substituted or unsubstituted methyl group and 60 silyl group are excluded from R_{30} , which is a substituent of ring CY₃. Due to this structure, the organometallic compound has excellent luminescence characteristics, and has such characteristics suitable for use as a luminescent material with high color purity by controlling the emission 65 wavelength range. In this regard, it is to be understood that the "substituted methyl group" is differentiated from a C₂ or higher alkyl group. Accordingly, in Table 1 below, Formulae

121

1 to 3 are not considered to include a “substituted methyl group.” Similarly, in Table 1 below, Formula B exemplifies the substituted methyl group as used in Table 1.


In one or more embodiments, the organometallic compound represented by Formula 1 may have excellent electrical mobility, and thus, electronic devices including the organometallic compound, for example, organic light-emitting devices including the organometallic compound may show low driving voltage, high efficiency, long lifespan, and reduced roll-off phenomenon.

In one or more embodiments, the photochemical stability of the organometallic compound represented by Formula 1 may be improved, and thus, electronic devices including the organometallic compound, for example, organic light-emitting devices including the organometallic compound, may show high emission efficiency, long lifespan, and high color purity.


The highest occupied molecular orbital (HOMO) energy level, lowest unoccupied molecular orbital (LUMO) energy level, energy gap (electron volts, eV), lowest excited triplet (T_1) energy level, and lowest excited singlet (S_1) energy level of selected organometallic compounds represented by Formula 1 were calculated using a density functional theory (DFT) method of the Gaussian 09 program with the molecular structure at the B3LYP level, and results thereof are shown in Table 1.

TABLE 1

Compound No.	HOMO (eV)	LUMO (eV)	Energy gap (eV)	S_1 (eV)	T_1 (eV)
Compound 1	-4.734	-1.329	3.405	2.765	2.475
Compound 2	-4.820	-1.362	3.458	2.796	2.519
Compound 3	-4.978	-1.445	3.533	2.839	2.556
Compound A	-4.727	-1.369	3.358	2.729	2.450
Compound B	-4.744	-1.311	3.433	2.786	2.493
Compound C	-4.760	-1.523	3.237	2.583	2.386



1






2

122

TABLE 1-continued

5	Compound No.	HOMO (eV)	LUMO (eV)	Energy gap (eV)	S_1 (eV)	T_1 (eV)
---	--------------	--------------	--------------	--------------------	---------------	---------------

10
15
330
35
A40
4555
60
B

65

123

TABLE 1-continued

Compound No.	HOMO (eV)	LUMO (eV)	Energy gap (eV)	S ₁ (eV)	T ₁ (eV)
C					

Referring to Table 1, it was confirmed that the organometallic compound represented by Formula 1 has electric characteristics that are desirable for a dopant in an electronic device, for example, an organic light-emitting device.

In one or more embodiments, the full width at half maximum (FWHM) of the emission peak of the emission spectrum or the electroluminescence spectrum of the organometallic compound may be 70 nanometers (nm) or less. For example, the FWHM of the emission peak of the emission spectrum or the electroluminescence spectrum of the organometallic compound may be from about 30 nm to about 65 nm, from about 40 nm to about 63 nm, or from about 45 nm to about 62 nm.

In one or more embodiments, the maximum emission wavelength (emission peak wavelength (λ_{max}), nm) of the emission peak of the emission spectrum or electroluminescence spectrum of the organometallic compound may be from about 500 nm to about 600 nm.

Synthesis methods of the organometallic compound represented by Formula 1 may be understood by a person having ordinary skill in the art by referring to Synthesis Examples provided herein.

The organometallic compound represented by Formula 1 is suitable for use in an organic layer of an organic light-emitting device, for example, for use as a dopant in an emission layer of the organic layer. Thus, another aspect provides an organic light-emitting device that includes a first electrode; a second electrode; and an organic layer located between the first electrode and the second electrode, wherein the organic layer includes an emission layer, and wherein the organic layer includes at least one organometallic compound represented by Formula 1.

As described herein, due to the inclusion of the organometallic compound represented by Formula 1 in the organic layer, the organic light-emitting device may have excellent characteristics in terms of driving voltage, current efficiency, power efficiency, external quantum efficiency (EQE), lifespan, and/or color purity. In addition, an organic light-emitting device may have a reduced roll-off phenomenon and a relatively narrow electroluminescent (EL) spectrum emission peak FWHM.

The organometallic compound represented by Formula 1 may be located between a pair of electrodes of an organic light-emitting device. For example, at least one organome-

124

talic compound represented by Formula 1 may be included in the emission layer. In this regard, the at least one organometallic compound may act as a dopant, and the emission layer may further include a host. In one or more embodiments, an amount of the organometallic compound represented by Formula 1 in the emission layer is less than an amount of the host in the emission layer.

In one or more embodiments, the emission layer may emit green light. For example, the emission layer may emit green light having a maximum emission wavelength of about 500 nm to about 600 nm.

The expression “(an organic layer) includes at least one of organometallic compounds” used herein may include a case in which “(an organic layer) includes a single organometallic compound represented by Formula 1” and a case in which “(an organic layer) includes two or more different organometallic compounds represented by Formula 1.”

For example, the organic layer may include, as the organometallic compound, only a single Compound 1. In this embodiment, Compound 1 may be included in the emission layer of the organic light-emitting device. In one or more embodiments, the organic layer may include, as the organometallic compound, Compound 1 and Compound 2. In this regard, Compound 1 and Compound 2 may be in the same layer (for example, Compound 1 and Compound 2 both may be in an emission layer).

The first electrode may be an anode, which is a hole injection electrode, and the second electrode may be a cathode, which is an electron injection electrode; or the first electrode may be a cathode, which is an electron injection electrode, and the second electrode may be an anode, which is a hole injection electrode.

In one or more embodiments, in the organic light-emitting device, the first electrode is an anode, and the second electrode is a cathode, and the organic layer may further include a hole transport region located between the first electrode and the emission layer, and an electron transport region located between the emission layer and the second electrode, the hole transport region may include a hole injection layer, a hole transport layer, an electron blocking layer, a buffer layer, or a combination thereof, and the electron transport region may include a hole blocking layer, an electron transport layer, an electron injection layer, or a combination thereof.

The term “organic layer” used herein refers to a single layer and/or a plurality of layers located between the first electrode and the second electrode of the organic light-emitting device. The “organic layer” may include, in addition to an organic compound, an organometallic complex including a metal.

The FIGURE is a schematic cross-sectional view of an organic light-emitting device 10 according to one or more embodiments. Hereinafter, the structure of an organic light-emitting device according to one or more embodiments of the present disclosure and a method of manufacturing an organic light-emitting device according to one or more embodiments of the present disclosure will be described in connection with the FIGURE. The organic light-emitting device 10 includes a first electrode 11, an organic layer 15, and a second electrode 19, which are sequentially stacked in this order.

125

A substrate may be additionally located under or beneath the first electrode 11 or above or on top of the second electrode 19. For use as the substrate, any substrate that is used in organic light-emitting devices, including those available in the art, may be used. In one or more embodiments, the substrate may be a glass substrate or a transparent plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

In one or more embodiments, the first electrode 11 may be formed by depositing or sputtering a material for forming the first electrode 11 on the substrate. The first electrode 11 may be an anode. The material for forming the first electrode 11 may be chosen from materials with a high work function to facilitate hole injection. The first electrode 11 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. The material for forming the first electrode 11 may be indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO_2), or zinc oxide (ZnO). In one or more embodiments, the material for forming the first electrode 11 may be metal, such as magnesium (Mg), aluminum (Al), silver (Ag), aluminum-lithium (Al-Li), calcium (Ca), magnesium-indium (Mg-In), or magnesium-silver (Mg-Ag).

The first electrode 11 may have a structure with a single layer, the first electrode 11 may have a structure including two or more layers. For example, the first electrode 11 may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode 11 is not limited thereto.

The organic layer 15 is located on the first electrode 11.

The organic layer 15 may include a hole transport region, an emission layer, and an electron transport region.

The hole transport region may be located between the first electrode 11 and the emission layer.

The hole transport region may include a hole injection layer, a hole transport layer, an electron blocking layer, a buffer layer, or a combination thereof.

The hole transport region may include only either a hole injection layer or a hole transport layer. In one or more embodiments, the hole transport region may have a hole injection layer/hole transport layer structure, or a hole injection layer/hole transport layer/electron blocking layer structure, wherein, for each structure, each layer is sequentially stacked in this stated order from the first electrode 11.

When the hole transport region includes a hole injection layer, the hole injection layer may be formed on the first electrode 11 by using one or more suitable methods, for example, vacuum deposition, spin coating, casting, and/or Langmuir-Blodgett (LB) deposition.

When a hole injection layer is formed by vacuum deposition, the deposition conditions may vary according to a material that is used to form the hole injection layer, and the structure and thermal characteristics of the hole injection layer. For example, the deposition conditions may include a deposition temperature of about 100° C. to about 500° C., a vacuum pressure of about 10^{-8} torr to about 10^{-3} torr, and a deposition rate of about 0.01 angstroms per second ($\text{\AA}/\text{s}$) to about 100 $\text{\AA}/\text{s}$. However, the deposition conditions are not limited thereto.

When the hole injection layer is formed using spin coating, coating conditions may vary according to the material used to form the hole injection layer, and the structure and thermal properties of the hole injection layer. For example, a coating speed may be from about 2,000 revolu-

126


tions per minute (rpm) to about 5,000 rpm, and a temperature at which a heat treatment is performed to remove a solvent after coating may be from about 80° C. to about 200° C. However, the coating conditions are not limited thereto.

The conditions for forming the hole transport layer and the electron blocking layer may be the same as the conditions for forming the hole injection layer.

The hole transport region may include at least one of


- 10 m-MTADATA, TDATA, 2-TNATA, NPB, β -NPB, TPD, Spiro-TPD, Spiro-NPB, methylated NPB, TAPC, HMTPD, 4,4',4"-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201 below, or a compound represented by Formula 202:

20



30


35



40

45


127
-continued



5

10

2-TNATA




25

30

35

NPB




40

45

50

β-NPB

128
-continued






15

20

25


Spiro-NPB



55


60

65



129

-continued



Formula 201

130

thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₁-C₆₀ alkylthio group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₇-C₆₀ alkyl aryl group, a C₇-C₆₀ aryl alkyl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a C₂-C₆₀ alkyl heteroaryl group, a C₂-C₆₀ heteroaryl alkyl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

5

10

15

20

25

30

35

40

45

50


55

60

65

60

Formula 202



Ar₁₀₁ and Ar₁₀₂ in Formula 201 may each independently be:

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chryselenylene group, a naphthacenylene group, a picenylene group, a peryenylene group, or a pentacenylene group; or

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chryselenylene group, a naphthacenylene group, a picenylene group, a peryenylene group, or a pentacenylene group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, or a C₁-C₁₀ alkoxy group, but embodiments of the present disclosure are not limited thereto.


R₁₀₉ in Formula 201 may be:

a phenyl group, a naphthyl group, an anthracenyl group, or a pyridinyl group; or

a phenyl group, a naphthyl group, an anthracenyl group, or a pyridinyl group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, or a pyridinyl group.


131

According to one or more embodiments, the compound represented by Formula 201 may be represented by Formula 201A, but embodiments of the present disclosure are not limited thereto:



R₁₀₁, R₁₁₁, R₁₁₂, and R₁₀₉ in Formula 201A may be understood by referring to the description provided herein for these substituent groups.

For example, the compound represented by Formula 201, or the compound represented by Formula 202 may include one or more of Compounds HT1 to HT20, but are not limited thereto:

**132**


-continued

HT2

HT3

133
-continued

HT4



5

10

15

20


25

30

35

40

HT5



45

50


55

60

65

134
-continued

HT6



5

10

15

20

25


30

35

40


HT5

HT7



135
-continued

HT8




5

10

20

HT9



25



30

35

HT10

40

45



50


55

60

65

136
-continued

HT11



5

10

15

20

HT9

25

30

35

40


45

50

55

60


65




HT12

HT13


-continued




HT14





HT15



HT16



HT16



A thickness of the hole transport region may be in the range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes at least one of a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may be in a range of about 50 Å to about

2,000 Å, for example, about 100 Å to about 1,500 Å. Without wishing to be bound to theory, when the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, satisfactory hole transport characteristics may be obtained without a substantial increase in driving voltage.



1

The hole transport region may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

The charge-generation material may be, for example, a p-dopant. The p-dopant may be a quinone derivative, a metal

139

oxide, or a cyano group-containing compound, but embodiments of the present disclosure are not limited thereto. Non-limiting examples of the p-dopant are a quinone derivative, for example, tetracyanoquinodimethane (TCNQ) or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinodimethane (F4-TCNQ); a metal oxide, for example, a tungsten oxide or a molybdenum oxide; or a cyano group-containing compound, such as one of Compounds HT-D1 or F12, but embodiments of the present description are not limited thereto.



The hole transport region may include a buffer layer.

Without wishing to be bound to theory, the buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, and thus, the efficiency of a formed organic light-emitting device may be improved.

An emission layer may be formed on the hole transport region by vacuum deposition, spin coating, casting, LB deposition, or the like. When the emission layer is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied in forming the hole injection layer although the deposition or coating conditions may vary according to a material that is used to form the emission layer.


When the hole transport region includes an electron blocking layer, a material for the electron blocking layer

140

may be a material for a hole transport region or a material for a host, as described herein. However, the material for the electron blocking layer is not limited thereto. For example, when the hole transport region includes an electron blocking layer, a material for the electron blocking layer may be mCP, as described herein in further detail.


The emission layer may include a host and a dopant, and the dopant may include at least one organometallic compound represented by Formula 1.

The host may include at least one of TPBi, TBADN, ADN (also referred to as "DNA"), CBP, CDBP, TCP, mCP, Compound H50, or Compound H51:




141


-continued




CDBP




TCP



MCP



H50




H51

142

In one or more embodiments, the host may further include a compound represented by Formula 301:

Formula 301



5

10

15

20

25

30

35

40

45

50

55

60

65

Ar₁₁₁ and Ar₁₁₂ in Formula 301 may each independently be:

a phenylene group, a naphthylene group, a phenanthrenylene group, or a pyrenylene group; or

a phenylene group, a naphthylene group, a phenanthrenylene group, or a pyrenylene group, each substituted with one or more of a phenyl group, a naphthyl group, or an anthracenyl group.


Ar₁₁₃ to Ar₁₁₆ in Formula 301 may each independently be: a C₁-C₁₀ alkyl group, a phenyl group, a naphthyl group, a phenanthrenyl group, or a pyrenyl group; or

a phenyl group, a naphthyl group, a phenanthrenyl group, or a pyrenyl group, each substituted with one or more of a phenyl group, a naphthyl group, or an anthracenyl group.

g, h, i, and j in Formula 301 may each independently be an integer from 0 to 4, and may be, for example, 0, 1, or 2.


Ar₁₁₃ and Ar₁₁₆ in Formula 301 may each independently be:a C₁-C₁₀ alkyl group that may be substituted with one or more of a phenyl group, a naphthyl group, or an anthracenyl group;

a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, or a fluorenyl group;

a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, or a fluorenyl group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₁-C₆₀ alkylthio group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, or a fluorenyl group; or

143

In one or more embodiments, the host may include a compound represented by Formula 302:



Formula 302 5

Ar₁₂₂ to Ar₁₂₅ in Formula 302 may be as described in further detail in connection with Ar₁₁₃ in Formula 301.

Ar₁₂₆ and Ar₁₂₇ in Formula 302 may each independently be a C₁-C₁₀ alkyl group (for example, a methyl group, an ethyl group, or a propyl group).

k and l in Formula 302 may each independently be an integer from 0 to 4. For example, k and l may be 0, 1, or 2.

When the organic light-emitting device is a full-color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and a blue emission layer. In one or more embodiments, due to a stacked structure including a red emission layer, a green emission layer, and/or a blue emission layer, the emission layer may emit white light. Other various embodiments are possible.

When the emission layer includes a host and a dopant, an amount of the dopant may be in a range of about 0.01 parts by weight to about 15 parts by weight based on 100 parts by weight of the host, but embodiments of the present disclosure are not limited thereto.

A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is within these ranges, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.


Then, an electron transport region may be located on the emission layer.

The electron transport region may include a hole blocking layer, an electron transport layer, an electron injection layer, or a combination thereof.


For example, the electron transport region may have a hole blocking layer/electron transport layer/electron injection layer structure or an electron transport layer/electron injection layer structure, and the structure of the electron transport region is not limited thereto. The electron transport layer may have a single-layered structure including a single material, or a multi-layered structure including two or more different materials.

Conditions for forming the hole blocking layer, the electron transport layer, and the electron injection layer, which constitute the electron transport region, may be understood by referring to the conditions described herein for forming the hole injection layer.

When the electron transport region includes a hole blocking layer, the hole blocking layer may include, for example, at least one of BCP, Bphen, or BAld, but embodiments of the present disclosure are not limited thereto.

144



BCP



Bphen

A thickness of the hole blocking layer may be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thickness of the hole blocking layer is within these ranges, excellent hole blocking characteristics may be obtained without a substantial increase in driving voltage.


The electron transport layer may include at least one of BCP, Bphen, Alq₃, BAld, TAZ, or NTAZ.

Alq₃


BAld

145

-continued



5



10

15


20

25


In one or more embodiments, the electron transport layer may include at least one of ET1 to ET25, but embodiments of the present description are not limited thereto:

146

-continued




ET3



ET4

ET1




30

35

40

45

ET2




50

55

60


65

ET5



US 12,391,714 B2

147
-continued




ET6

5

15

20

148



ET9

ET10

The chemical structure of ET7 is shown as a triphenylbenzene core. It features a central benzene ring fused with two hexaphenylbenzene rings. Each hexaphenylbenzene ring is further substituted with two 4-(4-pyridyl)phenyl groups, one on each side of the hexaphenylbenzene core.

四四

30

35

40

45

ET8
50


ET11

The chemical structure shows a central triphenylene core (three fused benzene rings) with two phenyl groups attached at the top and bottom positions. Each phenyl group is further substituted with a 4-(4-phenylbiphenyl-4-yl)phenyl group, which consists of a biphenyl unit (two fused benzene rings) attached to a phenyl ring, which is in turn attached to another phenyl ring.

US 12,391,714 B2


149
-continued

ET13



150
-continued



ET16



25

ET17



ET14






50

ET18

ET15




151
-continued



152
-continued

ET19




5

10

15

20

ET20




25

30

35

40

ET21



45

50

55

60

65

ET22


ET23

ET24

153

-continued


ET25




A thickness of the electron transport layer may be in the range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.

The electron transport layer may include a material including a metal in addition to the material as described hereinabove.

The material including a metal may be a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2:



ET-D1



ET-D2

The electron transport region may include an electron injection layer that promotes the flow of electrons from the second electrode 19 thereinto.

The electron injection layer may include LiF, NaCl, CsF, Li₂O, BaO, or a combination thereof.

A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within the range described above, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

The second electrode 19 is located on the organic layer 15. The second electrode 19 may be a cathode. A material for

154

forming the second electrode 19 may be a metal, an alloy, an electrically conductive compound, or a combination thereof, which have a relatively low work function. For example, lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) may be used as the material for forming the second electrode 19. In one or more embodiments, to manufacture a top-emission type light-emitting device, a transmissive electrode formed using ITO or IZO may be used as the second electrode 19.

Hereinbefore, the organic light-emitting device has been described with reference to the FIGURE, but embodiments of the present disclosure are not limited thereto.

Another aspect provides a diagnostic composition including at least one organometallic compound represented by Formula 1.

The organometallic compound represented by Formula 1 provides high luminescent efficiency. Accordingly, a diagnostic composition including the organometallic compound may have high diagnostic efficiency.

The diagnostic composition may be used in various applications including a diagnosis kit, a diagnosis reagent, a biosensor, and a biomarker.

The term “C₁-C₆₀ alkyl group” as used herein refers to a linear or branched saturated aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms, and non-limiting examples thereof include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an isoamyl group, and a hexyl group. The term “C₁-C₆₀ alkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

The term “C₁-C₆₀ alkoxy group” as used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group), and examples thereof include a methoxy group, an ethoxy group, and an isopropoxy group.

The term “C₂-C₆₀ alkenyl group” as used herein refers to a hydrocarbon group formed by substituting at least one carbon-carbon double bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethenyl group, a propenyl group, and a butenyl group. The term “C₂-C₆₀ alkynylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

The term “C₂-C₆₀ alkynyl group” as used herein refers to a hydrocarbon group formed by substituting at least one carbon-carbon triple bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethynyl group and a propynyl group. The term “C₂-C₆₀ alkynylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

The term “C₃-C₁₀ cycloalkyl group” as used herein refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms, and examples thereof include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. The term “C₃-C₁₀ cycloalkylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

The term “C₁-C₁₀ heterocycloalkyl group” as used herein refers to a monovalent saturated monocyclic group having at least one heteroatom that is N, O, P, Si, or S as a ring-forming atom instead of at least one carbon atom, and 1 to 10 carbon atoms, and non-limiting examples thereof include a tetrahydrofuranyl group and a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group” as used

herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkyl group.

The term "C₃-C₁₀ cycloalkenyl group" as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the ring thereof and no aromaticity, and non-limiting examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. The term "C₃-C₁₀ cycloalkenylene group" as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

The term "C₂-C₁₀ heterocycloalkenyl group" as used herein refers to a monovalent monocyclic group that has at least one heteroatom that is N, O, P, Si, or S as a ring-forming atom instead of at least one carbon, 2 to 10 carbon atoms, and at least one carbon-carbon double bond in its ring. Examples of the C₂-C₁₀ heterocycloalkenyl group are a 2,3-dihydrofuryl group and a 2,3-dihydrothiophenyl group. The term "C₂-C₁₀ heterocycloalkenylene group" as used herein refers to a divalent group having the same structure as the C₂-C₁₀ heterocycloalkenyl group.

The term "C₆-C₆₀ aryl group" as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and the term "C₆-C₆₀ arylen group" as used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Examples of the C₆-C₆₀ aryl group include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylen group each include two or more rings, the rings may be fused to each other. The term "C₇-C₆₀ alkyl aryl group" as used herein refers to a C₆-C₆₀ aryl group substituted with at least one C₁-C₆₀ alkyl group. The term "C₇-C₆₀ aryl alkyl group" as used herein refers to a C₁-C₆₀ alkyl group substituted with at least one C₁-C₆₀ aryl group.

The term "C₁-C₆₀ heteroaryl group" as used herein refers to a monovalent group having a cyclic aromatic system that has at least one heteroatom that is N, O, P, Si, or S as a ring-forming atom instead of at least one carbon atom, and 1 to 60 carbon atoms. The term "C₁-C₆₀ heteroarylene group" as used herein refers to a divalent group having a carbocyclic aromatic system that has at least one heteroatom that is N, O, P, Si, or S as a ring-forming atom instead of at least one carbon, and 1 to 60 carbon atoms. Examples of the C₁-C₆₀ heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₆-C₆₀ heteroarylene group each include two or more rings, the rings may be fused to each other. The term "C₂-C₆₀ alkyl heteroaryl group" as used herein refers to a C₁-C₆₀ heteroaryl group substituted with at least one C₁-C₆₀ alkyl group. The term "C₂-C₆₀ heteroaryl alkyl group" as used herein refers to a C₁-C₆₀ alkyl group substituted with at least one C₁-C₆₀ heteroaryl group.

The term "C₆-C₆₀ aryloxy group" as used herein refers to —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), and the term "C₆-C₆₀ arylthio group" as used herein refers to —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group).

The term "C₁-C₆₀ heteroaryloxy group" as used herein refers to —OA₁₀₄ (wherein A₁₀₄ is a C₁-C₆₀ heteroaryl group), and the term "C₁-C₆₀ heteroarylthio group" as used herein refers to —SA₁₀₅ (wherein A₁₀₅ is the C₁-C₆₀ heteroaryl group).

The term "monovalent non-aromatic condensed polycyclic group" as used herein refers to a monovalent group (for

example, having 8 to 60 carbon atoms) having two or more rings condensed to each other, only carbon atoms as ring-forming atoms, and no aromaticity in its entire molecular structure. Examples of the monovalent non-aromatic condensed polycyclic group include a fluorenyl group. The term "divalent non-aromatic condensed polycyclic group" as used herein refers to a divalent group having the same structure as a monovalent non-aromatic condensed polycyclic group.

The term "monovalent non-aromatic condensed heteropolycyclic group" as used herein refers to a monovalent group (for example, having 2 to 60 carbon atoms) having two or more rings condensed to each other, at least one heteroatom that is N, O, P, Si, or S instead of at least one carbon atom, as a ring-forming atom, and no aromaticity in its entire molecular structure. Examples of the monovalent non-aromatic condensed heteropolycyclic group include a carbazolyl group. The term "divalent non-aromatic condensed heteropolycyclic group" as used herein refers to a divalent group having the same structure as a monovalent non-aromatic condensed heteropolycyclic group.

The term "C₅-C₃₀ carbocyclic group" as used herein refers to a saturated or unsaturated cyclic group having, as a ring-forming atom, 5 to 30 carbon atoms only. The C₅-C₃₀ carbocyclic group may be a monocyclic group or a polycyclic group.

The term "C₁-C₃₀ heterocyclic group" as used herein refers to a saturated or unsaturated cyclic group having, as a ring-forming atom, at least one heteroatom that is N, O, P, Si, or S instead of at least one carbon ring atom, and 1 to 30 carbon atoms. The C₁-C₃₀ heterocyclic group may be a monocyclic group or a polycyclic group.

The term "TMS" as used herein refers to —Si(CH₃)₃, and the term "TMG" as used herein refers to —Ge(CH₃)₃.

At least one substituent of the substituted C₅-C₃₀ carbocyclic group, the substituted C₁-C₃₀ heterocyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₁-C₆₀ alkylthio group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₂-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₇-C₆₀ aryl alkyl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted C₂-C₆₀ alkyl heteroaryl group, the substituted C₂-C₆₀ heteroaryloxy group, the substituted C₁-C₆₀ heteroarylthio group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be:

deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof.

157

group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryloxy group, a C_1 - C_{60} heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —Ge(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₄)(Q₁₅), —B(Q₁₆)(Q₁₇), —P(Q₁₈)(Q₁₉), or —P(=O)(Q₁₈)(Q₁₉),
 a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryloxy group, a C_1 - C_{60} heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group;
 a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryloxy group, a C_1 - C_{60} heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_1 - C_{60} alkylthio group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_7 - C_{60} alkyl aryl group, a C_7 - C_{60} aryl alkyl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a C_2 - C_{60} alkyl heteroaryl group, a C_2 - C_{60} heteroarylthio group, a C_1 - C_{60} heteroaryloxy group, a C_1 - C_{60} heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —Ge(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₄)(Q₂₅), —B(Q₂₆)(Q₂₇), —P(Q₂₈)(Q₂₉), or —P(=O)(Q₂₈)(Q₂₉), —Si(Q₃₁)(Q₃₂)(Q₃₃), —Ge(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₄)(Q₃₅), —B(Q₃₆)(Q₃₇), —P(Q₂₈)(Q₂₉), or —P(=O)(Q₃₈)(Q₃₉), wherein Q₁ to Q₉, Q₁₁ to Q₁₉, Q₂₁ to Q₂₉, and Q₃₁ to Q₃₉ are each independently hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_1 - C_{60} alkylthio group, a


158

substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_7 - C_{60} alkyl aryl group, a substituted or unsubstituted C_7 - C_{60} aryl alkyl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_2 - C_{60} alkyl heteroaryl group, a substituted or unsubstituted C_2 - C_{60} heteroarylalkyl group, a C_1 - C_{60} heteroaryloxy group, a C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

Hereinafter, a compound and an organic light-emitting device according to one or more embodiments are described in further detail with reference to Synthesis Example and Examples. However, the organic light-emitting device is not limited thereto. The wording “B” was used instead of ‘A’ used in describing Synthesis Examples means that an amount of ‘A’ used was identical to an amount of ‘B’ used, in terms of a molar equivalent.


EXAMPLES

Synthesis Example 1: Synthesis of Compound 1




159

-continued

**160**

-continued



20 (1) Synthesis of Compound 1A

In a reaction vessel, 2-phenylpyridine (5.2 grams (g), 33.2 millimoles (mmol)) and iridium chloride (5.2 g, 14.7 mmol) were mixed with 120 milliliters (mL) of ethoxyethanol and 40 mL of deionized (DI) water, and the resultant mixture was stirred a reflux for 24 hours, and then, the temperature was allowed to cool to room temperature. The resulting solid was separated by filtration, washed sufficiently with water, methanol, and hexane, in this stated order, and then dried in a vacuum oven to obtain 8.2 g (yield of 92%) of Compound 1A.



25 (2) Synthesis of Compound 1B

In a reaction vessel, Compound 1A (1.6 g, 1.5 mmol) and 45 mL of methylene chloride (MC) were mixed, and then, 35 silver trifluoromethanesulfonate (silver triflate, AgOTf) (0.8 g, 3.1 mmol) was added thereto after being mixed with 15 mL of methanol (MeOH). Thereafter, the mixture was stirred for 18 hours at room temperature while light was excluded from the interior of the reaction vessel with aluminum foil, 40 and then the mixture was filtered through a diatomaceous earth plug to remove the resulting solid, and the filtrate was subjected to reduced pressure to obtain a solid (Compound 1B). Compound 1B was used in the next reaction without an additional purification process.

45 (3) Synthesis of Compound 1C

In a reaction vessel under a nitrogen environment, 4,4,5, 50 5-tetramethyl-2-(phenanthrene-2-yl)-1,3,2-dioxaborolane (3.7 g, 12.0 mmol) and 2-bromo-4-isopropyl-pyridine (2.0 g, 10.0 mmol) were dissolved in 140 mL of tetrahydrofuran (THF). Then, potassium carbonate (K_2CO_3) (3.2 g, 29.9 mmol) was dissolved in 25 mL of DI water, and then, the resultant solution was added to the tetrahydrofuran solution to form a reaction mixture, and a palladium catalyst ($Pd(PPh_3)_4$) (1.2 g, 1.2 mmol) was added thereto. Then, the reaction mixture was stirred at reflux at 100° C. for a period of time. After being allowed to cool to room temperature, a product was obtained by extraction and separated by filtration and the obtained solid was subjected to column chromatography (eluent: methylene chloride (MC) and hexane) to obtain 2.8 g (yield of 94%) of Compound 1C (4-isopropyl-2-(phenanthrene-2-yl)pyridine). The obtained compound was identified by high resolution mass spectrometry (HRMS, using matrix assisted laser desorption ionization, MALDI) and HPLC analysis.

65 HRMS (MALDI) calcd for $C_{22}H_{19}N$: m/z: 297.40 Found: 298.15



161


(4) Synthesis of Compound 1

In a reaction vessel, Compound 1B (1.5 g, 2.1 mmol) and Compound 1C (4-isopropyl-2-(phenanthrene-2-yl)pyridine) (0.7 g, 2.3 mmol) were mixed with 100 mL of 2-ethoxyethanol, the resultant mixture was stirred at reflux for 24 hours, and then, the temperature was allowed to cool to room temperature. The obtained mixture was subjected to a reduced pressure, and the obtained solid was then subjected to column chromatography (eluent: methylene chloride (MC) and hexane) to obtain 0.75 g (yield of 45%) of Compound 1. The obtained compound was identified by HRMS and HPLC analysis.

HRMS (MALDI) calcd for $C_{44}H_{34}IrN_3$: m/z: 796.99
Found: 798.24

162


-continued



2C

Synthesis Example 2: Synthesis of Compound 2

20



45 (1) Synthesis of Compound 2C


2.7 g (yield of 79%) of Compound 2C (6-isopropyl-3-(4-isopropyl-pyridin-2-yl) phenanthridine) was obtained using a method similar to the method of synthesizing Compound 50 1C in Synthesis Example 1, except that, when synthesizing Compound 1C, 6-isopropyl-3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenanthridine (4.2 g, 12.0 mmol) was used instead of 4,4,5,5-tetramethyl-2-(phenanthrene-2-yl)-1,3,2-dioxaborolane. The obtained compound was identified 55 by HRMS and HPLC analysis.

HRMS (MALDI) calcd for $C_{24}H_{24}N_2$: m/z: 340.47
Found: 341.19

60 (2) Synthesis of Compound 2





0.68 g (yield of 38%) of Compound 2 was obtained using a method similar to the method of synthesizing Compound 1 in Synthesis Example 1, except that Compound 2C (0.8 g, 2.3 mmol) was used instead of Compound 1C. The obtained compound was identified by HRMS and HPLC analysis.

HRMS (MADI) calcd for $C_{46}H_{39}IrN_4$: m/z: 840.06
Found: 841.28




163

Synthesis Example 3: Synthesis of Compound 3

**164**

-continued

**(1) Synthesis of Compound 3C**


2.9 g (yield of 85%) of Compound 3C (6-isopropyl-8-(4-isopropylpyridin-2-yl)phenanthridine) was obtained using a method similar to the method of synthesizing Compound 1C in Synthesis Example 1, except that, when synthesizing Compound 1C, 6-isopropyl-8-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenanthridine (4.2 g, 12.0 mmol) was used instead of 4,4,5,5-tetramethyl-2-(phenanthrene-2-yl)-1,3,2-dioxaborolane. The obtained compound was identified by HRMS and HPLC analysis.

HRMS (MALDI) calcd for $C_{24}H_{24}N_2$: m/z: 340.47
Found: 341.62

(2) Synthesis of Compound 3




0.80 g (yield of 45%) of Compound 2 was obtained using a method similar to the method of synthesizing Compound 1 in Synthesis Example 1, except that Compound 3C (0.8 g, 2.3 mmol) was used instead of Compound 1C. The obtained compound was identified by HRMS and HPLC analysis.

HRMS (MADI) calcd for $C_{46}H_{39}IrN_4$: m/z: 840.06
Found: 841.65


Synthesis Example 4: Synthesis of Compound 4

165

-continued



Ethoxylethanol
reflux, 24 h

**166**

(1) Synthesis of Compound 4C

2.2 g (yield of 85%) of Compound 4C (4-isobutyl-2-(phenanthrene-2-yl)-5-(trimethylgermyl)pyridine) was obtained using a method similar to the method of synthesizing Compound 1C in Synthesis Example 1, except that, when synthesizing Compound 1C, 2-bromo-4-isobutyl-5-(trimethylgermyl)pyridine (2.0 g, 6.0 mmol) was used instead of 2-bromo-4-isopropyl-pyridine. The obtained compound was identified by HRMS and HPLC analysis.

10 HRMS (MALDI) calcd for $C_{26}H_{29}GeN$: m/z: 428.16
Found: 430.11

(2) Synthesis of Compound 4

0.72 g (yield of 37%) of Compound 4 was obtained using a method similar to the method of synthesizing Compound 1 in Synthesis Example 1, except that Compound 4C (4-isobutyl-2-(phenanthrene-2-yl)-5-(trimethylgermyl)pyridine) (1.0 g, 2.3 mmol) was used instead of Compound 1C. The obtained compound was identified by HRMS and HPLC analysis.

20 HRMS (MALDI) calcd for $C_{48}H_{44}GeIrN_3$: m/z: 927.75
Found: 929.30


Example 1

25 As an anode, an ITO-patterned glass substrate was cut to a size of 50 mm×50 mm×0.5 mm, sonicated with isopropyl alcohol and DI water, each for 5 minutes, and then cleaned by exposure to ultraviolet rays and ozone for 30 minutes. The resultant glass substrate was loaded onto a vacuum deposition apparatus.

30 Compounds HT3 and F12(p-dopant) were co-deposited by vacuum on the anode at a weight ratio of 98:2 to form a hole injection layer having a thickness of 100 Å, and Compound HT3 was vacuum-deposited on the hole injection layer to form a hole transport layer having a thickness of 1,650 Å.






Then, GH3 (host) and Compound 1 (dopant) were co-deposited at a weight ratio of 92:8 on the hole transport layer to form an emission layer having a thickness of 400 Å.

40 Then, Compound ET3 and LiQ (n-dopant) were co-deposited on the emission layer at a volume ratio of 50:50 to form an electron transport layer having a thickness of 350 Å, LiQ was vacuum-deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Al was vacuum-deposited on the electron injection layer to form a cathode having a thickness of 1,000 Å, thereby completing the manufacture of an organic light-emitting device.



167

-continued



Examples 2 to 4 and Comparative Examples 1 to 3

Organic light-emitting devices were manufactured in a manner similar to the method of manufacturing in Example 1, except that Compounds shown in Table 2 were each used instead of Compound 1 as a dopant in forming an emission layer.


The driving voltage (volts, V), external quantum efficiency (EQE, %), maximum emission wavelength (λ_{max} , nm), and FWHM (nm) of each of the organic light-emitting devices manufactured according to Examples 1 to 4 and

168

Comparative Examples 1 to 3 were evaluated. Results thereof are shown in Table 2. A current-voltage meter (Keithley 2400) and a luminance meter (Minolta Cs-1000A) were used to obtain the data.


TABLE 2

	Dopant in emission layer	Driving voltage (V)	External quantum efficiency (%)	Maximum emission wavelength (nm)	FWHM (nm)
Example 1	Compound 1	4.2	21.5	524	78
Example 2	Compound 2	4.2	21.5	525	78
Example 3	Compound 3	4.2	20.5	515	76
Example 4	Compound 4	4.1	21.5	526	78
Comparative Example 1	Compound A	4.3	21.0	529	80
Comparative Example 2	Compound B	4.5	20.0	519	79
Comparative Example 3	Compound C	4.3	21.0	538	82




35

1



50

2




55

3

169

TABLE 2-continued

Dopant in emission layer	Driving voltage (V)	External quantum efficiency (%)	Maximum emission wavelength (nm)	FWHM (nm)
--------------------------	---------------------	---------------------------------	----------------------------------	-----------



Referring to Table 2, it has been shown that the organic light-emitting devices of Examples 1 to 4 have low driving

170

voltage, narrow FWHM, and excellent characteristics in terms of external quantum efficiency. In addition, it can be seen that the organic light-emitting devices of Examples 1 to 4 have a lower driving voltage, a similar level of or narrower FWHM, higher current efficiency, and a similar level of or higher external quantum efficiency than the organic light-emitting devices of Comparative Examples 1 to 3.

The organometallic compounds have excellent electrical characteristics and thermal stability. The organometallic compounds have a high glass transition temperature so that crystallization thereof may be limited and electric mobility thereof may be improved. Accordingly, an electronic device using the organometallic compounds described herein, for example, an organic light-emitting device using the organometallic compounds described herein, has a low driving voltage, high efficiency, a long lifespan, reduced roll-off ratio, and a relatively narrow EL spectrum emission peak FWHM.

Thus, due to the use of the organometallic compounds as described herein, a high-quality organic light-emitting device may be provided. Such organometallic compounds as described herein have excellent phosphorescent luminescent characteristics, and thus, when used for a diagnostic composition, a diagnostic composition having a high diagnostic efficiency may be provided.

It should be understood that exemplary embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each exemplary embodiment should typically be considered as available for other similar features or aspects in other embodiments. While one or more exemplary embodiments have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope as defined by the following claims.

What is claimed is:

1. An organometallic compound represented by Formula 1:

Formula 1

$$\text{M}_1(\text{Ln}_1)_{n_1}(\text{Ln}_2)_{n_2}$$

wherein, in Formula 1,

M_1 is a transition metal,

Ln_1 is a ligand represented by Formula 1A,


Ln_2 is a ligand represented by Formula 1B,

n_1 is 0, 1, or 2, and

n_2 is 1, 2, or 3,

55

Formula 1A



60

65

66

amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group; 5
a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a mono- 10
valent non-aromatic condensed polycyclic group, a mono- 15
valent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —Ge(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₄)(Q₁₅), —B(Q₁₆)(Q₁₇), —P(Q₈)(Q₉), or —P(=O)(Q₁₈)(Q₁₉), 20
a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a mono- 25
valent non-aromatic condensed polycyclic group, or a mono- 30
valent non-aromatic condensed heteropolycyclic group; 35
a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a mono- 40
valent non-aromatic condensed polycyclic group, or a mono- 45
valent non-aromatic condensed heteropolycyclic group, each substituted with one or more of deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group; 50
a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group, a C₁-C₆₀ alkylthio group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a mono- 55
valent non-aromatic condensed polycyclic group, a mono- 60
valent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —Ge(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₄)(Q₂₅), —B(Q₂₆)(Q₂₇), —P(Q₂₈)(Q₂₉), or —P(=O)(Q₂₈) (Q₂₉); or 65
—Si(Q₃₁)(Q₃₂)(Q₃₃), —Ge(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₄)(Q₃₅), —B(Q₃₆)(Q₃₇), —P(Q₃₈)(Q₃₉), or —P(=O)(Q₃₈)(Q₃₉), 70
wherein Q₁ to Q₉, Q₁₁ to Q₁₉, Q₂₁ to Q₂₉, and Q₃₁ to Q₃₉ are each independently hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a 75

nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_1-C_{60} alkylthio group, a substituted or unsubstituted C_3-C_{10} cycloalkyl group, a substituted or unsubstituted C_1-C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3-C_{10} cycloalkenyl group, a substituted or unsubstituted C_2-C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_7-C_{60} aryl aryl group, a substituted or unsubstituted C_6-C_{60} aryl alkyl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, a substituted or unsubstituted C_1-C_{60} heteroaryl group, a substituted or unsubstituted C_2-C_{60} alkyl heteroaryl group, a substituted or unsubstituted C_2-C_{60} heteroaryl alkyl group, a substituted or unsubstituted C_1-C_{60} heteroaryloxy group, a substituted or unsubstituted C_1-C_{60} heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and

wherein * and *[†] each indicate a binding site to M_1 .

. The organometallic compound of claim 1, wherein M_1 is iridium (Ir), platinum (Pt), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), thulium (Tm), or rhodium (Rh).

. The organometallic compound of claim 1, wherein M_1 is Ir, and


the sum of n_1 and n_2 is 3.

. The organometallic compound of claim 1, wherein Y_1 and CY_2 are each independently:

substituted or unsubstituted cyclopentane group, a substituted or unsubstituted cyclohexane group, a substituted or unsubstituted cycloheptane group, a substituted or unsubstituted cyclopentene group, a substituted or unsubstituted cyclohexene group, a substituted or unsubstituted cycloheptene group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthalene group, a substituted or unsubstituted 1,2,3,4-tetrahydronaphthalene group, a substituted or unsubstituted anthracene group, a substituted or unsubstituted phenanthrene group, a substituted or unsubstituted triphenylene group, a substituted or unsubstituted pyrene group, a substituted or unsubstituted chrysene group, a substituted or unsubstituted cyclopentadiene group, a substituted or unsubstituted thiophene group, a substituted or unsubstituted furan group, a substituted or unsubstituted indole group, a substituted or unsubstituted benzoborole group, a substituted or unsubstituted benzophosphole group, a substituted or unsubstituted indene group, a substituted or unsubstituted benzosilole group, a substituted or unsubstituted benzogermole group, a substituted or unsubstituted benzothiophene group, a substituted or unsubstituted benzoselenophene group, a substituted or unsubstituted benzofuran group, a substituted or unsubstituted carbazole group, a substituted or unsubstituted dibenzoborole group, a substituted or unsubstituted dibenzophosphole group, a substituted or unsubstituted fluorene group, a substituted or unsubstituted dibenz-

175

silole group, a substituted or unsubstituted dibenzogermole group, a substituted or unsubstituted dibenzothiophene group, substituted or unsubstituted a dibenzoselenophene group, a substituted or unsubstituted dibenzofuran group, a substituted or unsubstituted dibenzothiophene 5-oxide group, a substituted or unsubstituted 9H-fluoren-9-one group, a substituted or unsubstituted dibenzothiophene 5,5-dioxide group, a substituted or unsubstituted azaindole group, a substituted or unsubstituted azabenzoborole group, a substituted or unsubstituted azabenzophosphole group, a substituted or unsubstituted azaindene group, a substituted or unsubstituted azabenzosilole group, a substituted or unsubstituted azabenzogermole group, a substituted or unsubstituted azabenzothiophene group, a substituted or unsubstituted azabenzoselenophene group, a substituted or unsubstituted azabenzofuran group, a substituted or unsubstituted azacarbazole group, a substituted or unsubstituted azadibenzoborole group, a substituted or unsubstituted azadibenzophosphole group, a substituted or unsubstituted azafluorene group, a substituted or unsubstituted azadibenzosilole group, a substituted or unsubstituted azadibenzogermole group, a substituted or unsubstituted azadibenzoselenophene group, a substituted or unsubstituted azadibenzofuran group, a substituted or unsubstituted azadibenzothiophene 5-oxide group, a substituted or unsubstituted aza-9H-fluoren-9-one group, a substituted or unsubstituted azadibenzothiophene 5,5-dioxide group, a substituted or unsubstituted pyridine group, a substituted or unsubstituted pyrimidine group, a substituted or unsubstituted pyrazine group, a substituted or unsubstituted pyridazine group, a substituted or unsubstituted triazine group, a substituted or unsubstituted quinoline group, a substituted or unsubstituted isoquinoline group, a substituted or unsubstituted quinoxaline group, a substituted or unsubstituted quinazoline group, a substituted or unsubstituted phenanthroline group, a substituted or unsubstituted pyrrole group, a substituted or unsubstituted pyrazole group, a substituted or unsubstituted imidazole group, a substituted or unsubstituted triazole group, a substituted or unsubstituted oxazole group, a substituted or unsubstituted isoxazole group, a substituted or unsubstituted thiazole group, a substituted or unsubstituted isothiazole group, a substituted or unsubstituted oxadiazole group, a substituted or unsubstituted thiadiazole group, a substituted or unsubstituted benzopyrazole group, a substituted or unsubstituted benzimidazole group, a substituted or unsubstituted benzoxazole group, a substituted or unsubstituted benzothiazole group, a substituted or unsubstituted benzoxadiazole group, a substituted or unsubstituted benzothiadiazole group, a substituted or unsubstituted 5,6,7,8-tetrahydroisoquinoline group, or a substituted or unsubstituted 5,6,7,8-tetrahydroquinoline group; or a group represented by Formula 8-1 or 8-2:




Formula 8-1

60

65

176

-continued



Formula 8-2

wherein, in Formulae 8-1 and 8-2,

Y_{81} to Y_{84} are each independently a single bond, O, S, $N(R_{81})$, $C(R_{81})(R_{82})$, $Si(R_{81})(R_{82})$, $C(=O)$, $S(=O)$, $S(=O)_2$, $B(R_{81})$, $P(R_{81})$, or $P(=O)(R_{81})$,

CY_{81} to CY_{83} are each independently a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthalene group, a substituted or unsubstituted 1,2,3,4-tetrahydronaphthalene group, a substituted or unsubstituted phenanthrene group, a substituted or unsubstituted pyridine group, a substituted or unsubstituted pyrimidine group, a substituted or unsubstituted triazine group, a substituted or unsubstituted quinoline group, a substituted or unsubstituted isoquinoline group, a substituted or unsubstituted quinoxaline group, a substituted or unsubstituted quinazoline group, a substituted or unsubstituted phenanthroline group, a substituted or unsubstituted benzofuran group, a substituted or unsubstituted dibenzothiophene group, a substituted or unsubstituted dibenzosilole group, a substituted or unsubstituted azafluorene group, a substituted or unsubstituted azacarbazole group, a substituted or unsubstituted azadibenzofuran group, a substituted or unsubstituted azadibenzothiophene group, or a substituted or unsubstituted azadibenzosilole group, and

R_{81} and R_{82} are each independently as described in connection with R_{10} and R_{20} in claim 1.

5. The organometallic compound of claim 1, wherein CY_3 is a substituted or unsubstituted pyridine group, a substituted or unsubstituted pyrimidine group, a substituted or unsubstituted pyrazine group, a substituted or unsubstituted triazine group, a substituted or unsubstituted quinoline group, a substituted or unsubstituted isoquinoline group, a substituted or unsubstituted quinoxaline group, or a substituted or unsubstituted quinazoline group.


6. The organometallic compound of claim 1, wherein R_{10} , R_{20} , and R_{41} to R_{48} are each independently: hydrogen, deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, —Si(Q₁)(Q₂)(Q₃), or —Ge(Q₁)(Q₂)(Q₃), or

a group represented by one of Formulae 9-1 to 9-61, 9-201 to 9-237, 10-1 to 10-141, or 10-201 to 10-350:

9-1



9-2




9-3




US 12,391,714 B2

177
-continued
















178
-continued



US 12,391,714 B2

179


-continued



180


-continued

9-35




5

9-36




10

9-37




15

9-38




20

9-39




25

9-40




30

9-41




35

9-42




40

9-43




45

9-44




50

9-45




55

9-46



60

9-47



65

9-48

9-49

9-50

9-51

9-52

9-53

9-54

9-55

9-56


9-57

9-58


9-59

US 12,391,714 B2



181
-continued



182
-continued




US 12,391,714 B2

183
-continued**184**
-continued

US 12,391,714 B2


185

-continued



186












-continued



US 12,391,714 B2

187


-continued



188


-continued

10-31




5

10-32




10

10-33




15

10-34




20

10-35



25


10-36



30


35

10-37




40

10-38




45

10-39




50

10-40



55

10-41



60

10-42

10-43

10-44

10-45

10-46

10-47

10-48









10-49

10-50

US 12,391,714 B2

189


-continued



190


-continued

10-51




5

10-52




10

10-53




15

10-54




20

10-55




25

10-56




30

10-57




35

10-58



60

10-59



65

10-59

10-60

10-61

10-62

10-63

10-64

10-65

10-66










10-67

10-68








10-69

191









continued




192




US 12,391,714 B2

193
-continued**194**
-continued


10-85 10-93




10 10-94




15 10-95




20 10-88 10-96




25 10-89 10-97




30 10-90 10-98



35 10-91 10-99




40 10-92 10-100



45 50 55 60 65


US 12,391,714 B2

195




196

-continued




US 12,391,714 B2

197
-continued













198
-continued



US 12,391,714 B2


199

-continued

**200**

-continued

10-132



5

10-133

10


10-134

15

10-135

20

10-136 25




10-201

30

10-137

35



10-202


40

10-138

45

10-139

50



10-203


55

10-140

60

10-141


65




10-204

201

-continued










**202**

-continued




203

-continued


**204**

-continued


10-231




10-232




10-233




10-234




10-235




10-236




10-237



10-238



10-239



10-240

10-241

10-242

10-243

10-244


10-245

10-246


10-247

205

-continued

**206**








-continued



US 12,391,714 B2


207

-continued


**208**

-continued


10-264




10-265




10-266 20




10-267




30




10-268




40




10-269




50



10-270



60



65

10-271

10-272

10-273

10-274

10-275

10-276

10-277


10-278

10-279

US 12,391,714 B2


209

-continued




210


-continued



211
-continued










212
-continued



US 12,391,714 B2


213

-continued


**214**

-continued


10-321




10-322




10-323




10-324




10-325



10-326



10-327



10-328

10-329

10-330

10-331


10-332

10-333


10-334

215

-continued

**216**

-continued



wherein, in Formulae 9-1 to 9-61, 9-201 to 9-237, 10-1 to 10-141, or 10-201 to 10-350,

* indicates a binding site to a neighboring atom,

Ph is a phenyl group,

TMS is a trimethylsilyl group,

TMG is a trimethylgermyl group,

g5 is an integer from 1 to 5,

g10 is an integer from 1 to 10, and

g11 is an integer from 2 to 11.

7. The organometallic compound of claim 1, wherein

R_{30} is hydrogen, deuterium, —F, —Cl, —Br, —I, a C_2-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkyanyl group, a C_1-C_{60} alkoxy group, or —Ge(Q_1) $(Q_2)(Q_3)$, or

a group represented by one of Formulae 9-1 to 9-61, 9-201 to 9-237, 10-1 to 10-141, or 10-201 to 10-350:

9-1

9-2

9-3


9-4

10-344


65

US 12,391,714 B2

217
-continued




218
-continued




219

-continued


**220**

-continued




US 12,391,714 B2

221
-continued














222
-continued



US 12,391,714 B2


223

-continued

**224**


-continued

9-223




5

9-224




10

9-225




15

9-226



20

9-227



25

9-228



30

9-229



35

9-230



40

9-231



45

9-232



50

9-233



55

60

9-234

9-235

9-236

9-237

10-1

10-2

10-3

10-4

10-5

10-6













10-7

10-8

US 12,391,714 B2

225


-continued



226


-continued

10-9




5

10-10




10

10-11




15

10-12



20


10-13



TMG


25

10-14




30

10-15




35

10-16




40

10-17




45

10-18




50

10-19



55

10-20



60

10-21

10-21

10-22

10-23

10-24

10-25

10-26

10-27


10-28

10-29


10-30

10-31

227




228




US 12,391,714 B2

229

-continued


**230**

-continued




231

-continued









**232**

-continued




US 12,391,714 B2

233
-continued




234
-continued


10-86




10-87




10-88




10-89




10-90



10-91




10-92



10-93

60



65

10-94

10-95

10-96

10-97

10-98


10-99

10-100


10-101

US 12,391,714 B2

235
-continued




236
-continued




US 12,391,714 B2


237
-continued




238
-continued



239




240




241

-continued










**242**

-continued




243

-continued


**244**

-continued


10-231




10-232




10-233




10-234



10-235




10-236




35

10-237



45

10-238



55

10-239

60

10-240

10-241

10-242

10-243

10-244


10-245

10-246

10-247


US 12,391,714 B2

245



246








-continued



US 12,391,714 B2


247

-continued


**248**

-continued


10-264




10-265



10-266 20



10-267




30

10-271

35

10-275


10-268



40

10-276


10-269 45



50

10-277

10-270




60

10-278

65


10-279



US 12,391,714 B2


249

-continued




250

-continued




251

-continued

**252**








-continued



US 12,391,714 B2

253


-continued




254

-continued


10-321




10-322




10-323




10-324




10-325




10-326



50



10-327



10-328

10-329

10-330

10-331


10-332

10-333


10-334

255

-continued

**256**

-continued



wherein, in Formulae 9-1 to 9-61, 9-201 to 9-237, 10-1 to 10-141, and 10-201 to 10-350,

* indicates a binding site to a neighboring atom,

Ph is a phenyl group,

TMS is a trimethylsilyl group,

TMG is a trimethylgermyl group,


g5 is an integer from 1 to 5,

g10 is an integer from 1 to 10, and

g11 is an integer from 2 to 11.

8. The organometallic compound of claim 1, wherein


CY₁ is represented by one of Formulae 1-1 to 1-16:



US 12,391,714 B2



257

-continued



259

-continued



wherein, in Formulae 1-1 to 1-16,

X₁₁ is O, S, N(R_{19a}), C(R_{19a})(R_{19b}), or Si(R_{19a})(R_{19b}),
R₁₁ to R₁₈, R_{19a}, and R_{19b} are each independently as
described in connection with R₁₀ in claim 1,

two or more neighboring substituents of R₁₁ to R₁₈, R_{19a},
or R_{19b} are optionally linked to each other to form a
substituted or unsubstituted C₅-C₃₀ carbocyclic group
or a substituted or unsubstituted C₁-C₃₀ heterocyclic
group, and

wherein, when R₁₁ to R₁₈, R_{19a}, or R_{19b} is —Si(Q₁)(Q₂)
(Q₃) or —Ge(Q₁)(Q₂)(Q₃), to Q₃ are each indepen-

dently:
—CH₃, —CD₃, —CD₂H, —CDH₂, —CH₂CH₃,
—CH₂CD₃, —CH₂CD₂H, —CH₂CDH₂, —CHDCH₃,
—CHDCD₂H, —CHDCDH₂, —CHDCD₃,
—CD₂CD₃, —CD₂CD₂H, or —CD₂CDH₂;

an n-propyl group, an isopropyl group, an n-butyl group,
an isobutyl group, a sec-butyl group, a tert-butyl group,
an n-pentyl group, an isopentyl group, a sec-pentyl
group, a tert-pentyl group, a phenyl group, or a naph-
thyl group; or


an n-propyl group, an isopropyl group, an n-butyl group,
an isobutyl group, a sec-butyl group, a tert-butyl group,
an n-pentyl group, an isopentyl group, a sec-pentyl
group, a tert-pentyl group, a phenyl group, or a naph-
thyl group, each substituted with one or more of
deuterium, a C₁-C₁₀ alkyl group, or a phenyl group,

* indicates a binding site to M₁, and

*† indicates a binding site to CY₂.


9. The organometallic compound of claim 1, wherein

CY₂ is represented by one of Formulae 2-1 to 2-22:




1-15

5




10

15



20



2-2

2-3

2-4

2-5

2-6



2-7

2-8

35


40

45



60


65



US 12,391,714 B2


261

-continued




262

-continued











263

-continued








**264*** indicates a binding site to CY₁, and*† indicates a binding site to M₁.10. The organometallic compound of claim 1, wherein CY₃ is represented by one of Formulae 3-1 to 3-16:

3-1



265

-continued



wherein, in Formulae 3-1 to 3-16,

R₃₁ to R₃₄ are each independently as described in connection with R₃₀ in claim 1, and* indicates a binding site to M₁, and

** indicates a binding site to a neighboring atom.

266

11. The organometallic compound of claim 1, wherein the organometallic compound is a compound represented by Formula 11-1:

3-10

5

3-11

10

3-12

15

20

3-13 25

30

3-14

35

3-15 40

45


3-16

55

60

65

Formula 11-1




wherein, in Formula 11-1,

M₁, n1, n2, CY₁, CY₂, Y₁ to Y₈, R₁₀, R₂₀, b10, and b20 each are as described in claim 1,X₃₁ is C(R₃₁) or N, X₃₂ is C(R₃₂) or N, X₃₃ is C(R₃₃) or N, and X₃₄ is C(R₃₄) or N,R₃₁ to R₃₄ are each independently as described in connection with R₃₀ in claim 1, andtwo or more of R₃₁ to R₃₄ are optionally linked to form a substituted or unsubstituted C₅-C₃₀ carbocyclic group or a substituted or unsubstituted C₁-C₃₀ heterocyclic group.

12. The organometallic compound of claim 1, wherein the organometallic compound is a compound represented by Formula 12-1:

Formula 12-1






wherein, in Formula 12-1,

M₁, n1, n2, CY₁, CY₂, R₁₀, R₂₀, b10, b20, and R₄₁ to R₄₈ are each as described in claim 1, andR₃₁ to R₃₄ are each independently as described in connection with R₃₀ in claim 1.

13. The organometallic compound of claim 1, wherein the organometallic compound is electrically neutral.




267

14. The organometallic compound of claim 1, wherein
the organometallic compound is one of Compounds 1 to
179:


**268**

-continued









4







6



7


269
-continued**270**
-continued

271
-continued




272
-continued


16




17




18




19 50




273
-continued




24




5




10




15




20




25




30




35




40



45




50




274
-continued


28




5




10




15




20




25




30




35




40



45




50



29


30

275
-continued




31
5
10
15
20

276
-continued




34




25
32
30
35
40

35




45






33
50
55
60
65

36




277
-continued




278
-continued


37 40




5 15 20 41







25 30 35 42




39 45 50 43



279
-continued**280**
-continued

44




5

10

15

48




20

25

30

49



46

35


40

50

50

47

51




55

60


65

281


-continued




52



53




54




55

282


-continued




56



57




58




59

283


-continued




60



61




62




63

284


-continued




64



65



66




67

285

-continued

68



5

10


15

20

286

-continued


71



25

69

72




30

35

40


45



50

70


73



55


60

65




287


-continued




74



75




76 35




77 50

288


-continued




78



79




80




81

289


-continued




82



83




84




85 50

290


-continued



86



87




88

65

291


-continued





89

292



-continued



92

25
90


93

45
91

94

293

-continued



95

5

10

15

20

25

30

35

40

45

50


55

60


65

294

-continued



98



96

99

40



45

50

55

60


65



100

295

-continued




101


20

296

-continued




104



102

105

45



103


106

50

55

60


65



297

-continued

107



5

10


15

20

298

-continued


110



108

25

111



30

35


40

45

109

50


112







55

60

65




299
-continued




300
-continued


113 5 10 15 117




114 20 25 30 118



115 35 40 45 119




116 50 55 60 120




65

301


-continued




121



122




123




124 50

302


-continued




125



126




127



128

303


-continued




129

304


-continued




132




130




133




35



134











131 50



135


305

-continued



307
-continued


144




15

308
-continued

148




145




20

146 35




149




40

147




150



55


60




151

309


-continued




152




153



154




155




156

310

-continued




157



158

311
-continued



159


5

10


15

20

312
-continued



162

25
160



30

40

35

45

163



161


50

55

60


65

164



313

-continued




165

5

10

15

166



25


30

35

40

45

167



50


55

60


65

314


-continued



168



169




170

315

-continued

171



5

10

15

20

25


30

35

40

45

173



50

55



60

65


316

-continued

174




175



176

317

-continued

**318****15.** An organic light-emitting device, comprising:

a first electrode;

a second electrode; and

an organic layer located between the first electrode and the second electrode,

wherein the organic layer comprises an emission layer, and

wherein the organic layer comprises at least one of the organometallic compound of claim 1.

16. The organic light-emitting device of claim 15, wherein the emission layer comprises the at least one organometallic compound.**17.** The organic light-emitting device of claim 16, wherein the emission layer further comprises a host, and

the amount of the host in the emission layer is greater than the amount of the at least one organometallic compound in the emission layer.

18. The organic light-emitting device of claim 17, wherein the emission layer emits green light having a maximum emission wavelength of about 500 nanometers to about 600 nanometers.**19.** The organic light-emitting device of claim 16, wherein the first electrode is an anode,

the second electrode is a cathode,

the organic layer further comprises a hole transport region located between the first electrode and the emission layer, and an electron transport region located between the emission layer and the second electrode, wherein the hole transport region comprises a hole injection layer, a hole transport layer, an electron blocking layer, a buffer layer, or a combination thereof, and

the electron transport region comprises a hole blocking layer, an electron transport layer, an electron injection layer, or a combination thereof.

20. A diagnostic composition comprising at least one of the organometallic compound of claim 1.

* * * * *