

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250259976

Kind Code

A1

Publication Date

August 14, 2025

Inventor(s)

Yu; Chen-Hua et al.

INTEGRATED CIRCUIT PACKAGE AND METHOD

Abstract

In an embodiment, a structure includes: a processor device including logic devices; a first memory device directly face-to-face bonded to the processor device by metal-to-metal bonds and by dielectric-to-dielectric bonds; a first dielectric layer laterally surrounding the first memory device; a redistribution structure over the first dielectric layer and the first memory device, the redistribution structure including metallization patterns; and first conductive vias extending through the first dielectric layer, the first conductive vias connecting the metallization patterns of the redistribution structure to the processor device.

Inventors: Yu; Chen-Hua (Hsinchu, TW), Chang; Wei Ling (Hsinchu, TW), Wang; Chuei-Tang (Taichung City, TW), Chen; Chieh-Yen (Taipei City, TW)

Applicant: Taiwan Semiconductor Manufacturing Co., Ltd. (Hsinchu, TW)

Family ID: 75269025

Appl. No.: 19/192484

Filed: April 29, 2025

Related U.S. Application Data

parent US continuation 18593536 20240301 parent-grant-document US 12315854 child US 19192484

parent US continuation 17854386 20220630 parent-grant-document US 11948926 child US 18593536

parent US continuation 16882054 20200522 parent-grant-document US 11387222 child US 17854386

us-provisional-application US 62923161 20191018

Publication Classification

Int. Cl.: H01L25/16 (20230101); **H01L23/00** (20060101)

U.S. Cl.:

CPC H01L25/16 (20130101); **H01L24/19** (20130101); **H01L24/20** (20130101); **H01L24/27** (20130101); **H01L24/29** (20130101); H01L2924/12 (20130101); H01L2924/1431 (20130101); H01L2924/1434 (20130101)

Background/Summary

PRIORITY CLAIM AND CROSS-REFERENCE [0001] This application is a continuation of U.S. Patent Ser. No. 18/593,536, filed on Mar. 1, 2024, entitled “Integrated Circuit Package and Method,” which is a continuation of U.S. Patent Ser. No. 17/854,386, filed on Jun. 30, 2022, entitled “Integrated Circuit Package and Method,” now U.S. Pat. No. 11,948,926, issued on Apr. 2, 2024, which is a continuation of U.S. Patent Ser. No. 16/882,054, filed on May 22, 2020, entitled “Integrated Circuit Package and Method,” now U.S. Pat. No. 11,387,222, issued on Jul. 12, 2022, which claims the benefit of U.S. Provisional Application No. 62/923,161, filed on Oct. 18, 2019, which applications are hereby incorporated herein by reference.

BACKGROUND

[0002] As semiconductor technologies continue to evolve, integrated circuit dies are becoming increasingly smaller. Further, more functions are being integrated into the dies. Accordingly, the numbers of input/output (I/O) pads needed by dies has increased while the area available for the I/O pads has decreased. The density of the I/O pads has risen quickly over time, increasing the difficulty of die packaging. Some applications call for greater parallel processing capabilities of integrated circuit dies. Packaging technologies may be used to integrate of multiple dies, allowing a greater degree of parallel processing capabilities.

[0003] In some packaging technologies, integrated circuit dies are singulated from wafers before they are packaged. An advantageous feature of this packaging technology is the possibility of forming fan-out packages, which allow the I/O pads on a die to be redistributed to a greater area. The number of I/O pads on the surfaces of the dies may thus be increased.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0004] Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

[0005] FIGS. **1** through **10** are various views of intermediate steps during a process for forming an integrated circuit package, in accordance with some embodiments.

[0006] FIGS. **11** and **12** are cross-sectional views of intermediate steps during a process for forming a system implementing an integrated circuit package, in accordance with some embodiments.

[0007] FIGS. **13**, **14**, **15**, **16**, and **17** are cross-sectional views of intermediate steps during a process for forming a system implementing an integrated circuit package, in accordance with some other embodiments.

[0008] FIGS. **18** through **24** are various views of intermediate steps during a process for forming an integrated circuit package, in accordance with some other embodiments.

[0009] FIG. **25** is a cross-sectional view of a system implementing an integrated circuit package, in accordance with some other embodiments.

[0010] FIG. **26** is a cross-sectional view of a system implementing an integrated circuit package, in accordance with some other embodiments.

[0011] FIGS. **27** through **31** are various views of intermediate steps during a process for forming an integrated circuit package, in accordance with some other embodiments.

[0012] FIG. **32** is a cross-sectional view of a system implementing an integrated circuit package, in accordance with some other embodiments.

[0013] FIG. **33** is a cross-sectional view of a system implementing an integrated circuit package, in accordance with some other embodiments.

DETAILED DESCRIPTION

[0014] The following disclosure provides many different embodiments, or examples, for implementing different features of the invention. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

[0015] Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

[0016] In accordance with some embodiments, a processor device is formed without memories, and an integrated circuit package is formed by stacking memory devices on the processor device. Forming a processor device without memories allows more processing units (e.g., cores) to be included in the processor device without substantially increasing the footprint of the processor device. The processor device and memory devices are connected (e.g., physically and electrically coupled) by hybrid bonding. Connecting the processor device and memory devices by hybrid bonding allows the connections between the devices to be shorter than traditional interconnects, allowing for improvements in the performance and power consumption of the integrated circuit package.

[0017] FIGS. **1** through **10** are various views of intermediate steps during a process for forming an integrated circuit package **100**, in accordance with some embodiments. FIGS. **1** through **9** are cross-sectional views of the integrated circuit package **100**, and FIG. **10** is a three-dimensional diagram illustrating electrical connections among the semiconductor devices of the integrated circuit package **100**, where the cross-sectional views are illustrated along reference cross-section X-X in FIG. **10**. Some features are omitted from FIG. **10** for clarity of illustration.

[0018] The integrated circuit package **100** is formed by stacking semiconductor devices on a wafer **102**. Stacking of devices in one device region **102A** of the wafer **102** is illustrated, but it should be appreciated that the wafer **102** may have any number of device regions, and semiconductor devices may be stacked to form an integrated circuit package in each device region. The semiconductor devices can be bare integrated circuit dies or packaged dies. In the embodiment illustrated, each semiconductor device is a bare integrated circuit die. In other embodiments, one or more of the

illustrated semiconductor devices can be packaged dies that are encapsulated.

[0019] In FIG. 1, the wafer **102** is obtained. The wafer **102** comprises a processor device **10** in the device region **102A**. The processor device **10** will be singulated in subsequent processing to be included in the integrated circuit package **100**. The processor device **10** can be any acceptable processor or logic device, such as a central processing unit (CPU), graphics processing unit (GPU), system-on-a-chip (SoC), application processor (AP), digital signal processing (DSP), field programmable gate array (FPGA), microcontroller, artificial intelligence (AI) accelerator, or the like.

[0020] The processor device **10** may be processed according to applicable manufacturing processes to form integrated circuits. For example, the processor device **10** includes a semiconductor substrate **12**, such as silicon, doped or undoped, or an active layer of a semiconductor-on-insulator (SOI) substrate. The semiconductor substrate **12** may include other semiconductor materials, such as germanium; a compound semiconductor including silicon carbide, gallium arsenic, gallium phosphide, indium phosphide, indium arsenide, and/or indium antimonide; an alloy semiconductor including SiGe, GaAsP, AlInAs, AlGaAs, GaInAs, GaInP, and/or GaInAsP; or combinations thereof. Other substrates, such as multi-layered or gradient substrates, may also be used. The semiconductor substrate **12** has an active surface **12A** and an inactive surface **12N**.

[0021] Devices may be formed at the active surface **12A** of the semiconductor substrate **12**. The devices may be active devices (e.g., transistors, diodes, etc.), capacitors, resistors, etc. The inactive surface **12N** may be free from devices. An inter-layer dielectric (ILD) is over the active surface **12A** of the semiconductor substrate **12**. The ILD surrounds and may cover the devices. The ILD may include one or more dielectric layers formed of materials such as Phospho-Silicate Glass (PSG), Boro-Silicate Glass (BSG), Boron-Doped Phospho-Silicate Glass (BPSG), undoped Silicate Glass (USG), or the like.

[0022] An interconnect structure **14** is over the active surface **12A** of the semiconductor substrate **12**. The interconnect structure **14** interconnects the devices at the active surface **12A** of the semiconductor substrate **12** to form an integrated circuit. The interconnect structure **14** may be formed by, for example, metallization patterns in dielectric layers. The metallization patterns include metal lines and vias formed in one or more dielectric layers. The metallization patterns of the interconnect structure **14** are electrically coupled to the devices at the active surface **12A** of the semiconductor substrate **12**.

[0023] Die connectors **16** are at a front side **10F** of the processor device **10**. The die connectors **16** may be conductive pillars, pads, or the like, to which external connections are made. The die connectors **16** are in and/or on the interconnect structure **14**. The die connectors **16** can be formed of a metal, such as copper, aluminum, or the like, and can be formed by, for example, plating, or the like.

[0024] A dielectric layer **18** is at the front side **10F** the processor device **10**. The dielectric layer **18** is in and/or on the interconnect structure **14**. The dielectric layer **18** laterally encapsulates the die connectors **16**, and the dielectric layer **18** will be laterally coterminous with sidewalls of the processor device **10** after singulation (discussed further below). Initially, the dielectric layer **18** may bury the die connectors **16**, such that the topmost surface of the dielectric layer **18** is above the topmost surfaces of the die connectors **16**. The dielectric layer **18** may be an oxide such as silicon oxide, PSG, BSG, BPSG, or the like; a nitride such as silicon nitride or the like; a polymer such as PBO, polyimide, BCB, or the like; the like; or a combination thereof. The dielectric layer **18** may be formed, for example, by spin coating, lamination, chemical vapor deposition (CVD), or the like. After formation, the die connectors **16** and dielectric layer **18** can be planarized using, e.g., a chemical-mechanical polish (CMP) process, an etch back process, the like, or combinations thereof. After planarization, surfaces of the die connectors **16** and dielectric layer **18** are planar and are exposed at the front side **10F** of the processor device **10**.

[0025] In some embodiments, the processor device **10** is a CPU that includes multiple processing

units (e.g., cores). For example, referring to FIG. 10, the processor device **10** can be a quad-core processor that comprises a first processing unit **10A** in a first region of the semiconductor device, a second processing unit **10B** in a second region of the semiconductor device, a third processing unit **10C** in a third region of the semiconductor device, and a fourth processing unit **10D** in a fourth region of the semiconductor device. The processing units of the processor device **10** are formed without (e.g., are free from) memories, and only include logic devices. In other words, the processor device **10** does not include memory devices such as DRAM, SRAM, etc. devices. As discussed further below, separate memory devices will be stacked on the processor device **10** to provide memories for the processing units.

[0026] In FIG. 2, first memory devices **20** are bonded to the processor device **10** (e.g., the wafer **102**). The first memory devices **20** can be any acceptable memory devices, such as dynamic random access memory (DRAM) devices, static random access memory (SRAM) devices, resistive random-access memory (RRAM) devices, magnetoresistive random-access memory (MRAM) devices, phase-change random-access memory (PCRAM) devices, or the like.

[0027] Each first memory device **20** may be processed according to applicable manufacturing processes to form integrated circuits. For example, the first memory device **20** includes a semiconductor substrate **22**, an interconnect structure **24**, die connectors **26**, and a dielectric layer **28** which, respectively, can be similar to the semiconductor substrate **12**, interconnect structure **14**, die connectors **16**, and dielectric layer **18**. The die connectors **26** and dielectric layer **28** are exposed at a front side **20F** of the first memory device **20**. The first memory device **20** further includes conductive vias **30**, which are formed extending into the semiconductor substrate **22**. The conductive vias **30** are electrically coupled to metallization patterns of the interconnect structure **24**.

[0028] As an example to form the conductive vias **30**, recesses can be formed in the interconnect structure **24** and/or semiconductor substrate **22** by, for example, etching, milling, laser techniques, a combination thereof, and/or the like. A thin dielectric material may be formed in the recesses, such as by using an oxidation technique. A thin barrier layer may be conformally deposited in the openings, such as by CVD, atomic layer deposition (ALD), physical vapor deposition (PVD), thermal oxidation, a combination thereof, and/or the like. The barrier layer may be formed from an oxide, a nitride, or an oxynitride, such as titanium nitride, titanium oxynitride, tantalum nitride, tantalum oxynitride, tungsten nitride, a combination thereof, and/or the like. A conductive material may be deposited over the barrier layer and in the openings. The conductive material may be formed by an electro-chemical plating process, CVD, ALD, PVD, a combination thereof, and/or the like. Examples of conductive materials are copper, tungsten, aluminum, silver, gold, a combination thereof, and/or the like. Excess conductive material and barrier layer is removed from the surface of the interconnect structure **24** and/or semiconductor substrate **22** by, for example, a CMP. Remaining portions of the barrier layer and conductive material form the conductive vias **30**.

[0029] In the embodiment illustrated, the conductive vias **30** are not yet exposed at a back side **20B** of the first memory device **20**. Rather, the conductive vias **30** are buried in the semiconductor substrate **22**. As discussed further below, the conductive vias **30** will be exposed at the back side **20B** of the first memory device **20** through a planarization process in subsequent processing. After exposure, the conductive vias **30** can be referred to as through-substrate vias or through-silicon vias (TSVs).

[0030] In some embodiments, the first memory devices **20** are memories for the processor device **10**. For example, the first memory devices **20** can be level 1 (L1) caches for the processor device **10**. Bonding the first memory devices **20** to the processor device **10** instead of including memories with the processor device **10** may allow the overall amount of memory in the integrated circuit package **100** to be increased without substantially increasing manufacturing costs of the processor devices. Further, forming the processor device **10** without memories allows more processing units (e.g., cores) to be included in the processor devices without substantially increasing the footprint of

the processor devices. Processors with many processing units can be particularly for some applications, such as artificial intelligence (AI) and high- performance computing (HPC) applications.

[0031] Referring to FIG. **10**, two of the first memory devices **20** can be placed on each processing unit of the processor device **10**. For example, when the integrated circuit package **100** follows the von Neumann architecture, an instruction cache device **201** (e.g., a L1i cache) and a data cache device **20D** (e.g., a L1d cache) are stacked directly over each region of the processor device **10** corresponding to the processing units **10A**, **10B**, **10C**, **10D**. The instruction cache devices **201** are used to speed up executable instruction fetches for the processor device **10**, and the data cache devices **20D** are used to speed up data fetch and store operations for the processor device **10**. Placing the first memory devices **20** directly over their corresponding processing units **10A**, **10B**, **10C**, **10D** allows the length of interconnections between logic devices and their corresponding memories to be reduced. The first memory devices **20** are connected to the processor device **10** by direct bonds, over which control signaling and data signaling are performed. The latency of data signaling and the interconnection bandwidth between the processor device **10** and their corresponding first memory devices **20** may thus be improved. Further, the impedance and thus power consumption of the interconnections may also be reduced.

[0032] The processor device **10** and first memory devices **20** are directly bonded in a face-to-face manner by hybrid bonding, such that the front side **10F** of the processor device **10** is bonded to the front sides **20F** of the first memory devices **20**. Specifically, the dielectric layer **18** of the processor device **10** is bonded to the dielectric layers **28** of the first memory devices **20** through dielectric-to-dielectric bonding, without using any adhesive material (e.g., die attach film), and a subset of the die connectors **16A** of the processor device **10** are bonded to the die connectors **26** of the first memory devices **20** through metal-to-metal bonding, without using any eutectic material (e.g., solder). The bonding may include a pre-bonding and an annealing. During the pre-bonding, a small pressing force is applied to press the first memory devices **20** against the processor device **10** (e.g., the wafer **102**). The pre-bonding is performed at a low temperature, such as room temperature, such as a temperature in the range of about 15° C. to about 30° C., and after the pre-bonding, the dielectric layers **18** and **28** are bonded to each other. The bonding strength is then improved in a subsequent annealing step, in which the dielectric layers **18** and **28** are annealed at a high temperature, such as a temperature in the range of about 100° C. to about 450° C. After the annealing, bonds, such as fusions bonds, are formed bonding the dielectric layers **18** and **28**. For example, the bonds can be covalent bonds between the material of the dielectric layer **18** and the material of the dielectric layer **28**. The die connectors **16A** and **26** are connected to each other with a one-to-one correspondence. The die connectors **16A** and **26** may be in physical contact after the pre-bonding, or may expand to be brought into physical contact during the annealing. Further, during the annealing, the material of the die connectors **16A** and **26** (e.g., copper) intermingles, so that metal-to-metal bonds are also formed. Hence, the resulting bonds between the processor device **10** and first memory devices **20** are hybrid bonds that include both dielectric-to-dielectric bonds and metal-to-metal bonds.

[0033] The first memory devices **20** have active devices of a minimum feature size in the range of about 2 nm to about 65 nm. As such, the die connectors **26** of the first memory devices **20** can have a small pitch. For example, the die connectors **26** can have a pitch in the range of about 0.05 μm to about 10 μm . The die connectors **16A** have the same pitch as the die connectors **26**. Forming the die connectors **16A** and **26** at a small pitch allows for a large quantity of connections between the processor device **10** and the first memory devices **20**, which can be particularly advantageous when the first memory devices **20** are L1 caches.

[0034] Optionally, passive devices **40** are also bonded to the processor device **10** (e.g., the wafer **102**). The passive devices **40** can be any acceptable passive devices, such as integrated passive devices (IPDs), power management integrated circuits (PMICs), integrated voltage regulators

(IVRs), or the like.

[0035] Each passive device **40** may be processed according to applicable manufacturing processes to form integrated circuits. For example, the passive device **40** includes a semiconductor substrate **42**, which can be similar to the semiconductor substrate **12**, but includes passive devices (e.g., resistors, capacitors, inductors, etc.) and is free of active devices (e.g., transistors, diodes, etc.). The passive device **40** also includes an interconnect structure **44**, die connectors **46**, a dielectric layer **48**, and conductive vias **50** which, respectively, can be similar to the interconnect structure **14**, die connectors **16**, dielectric layer **18**, and conductive vias **30**. The die connectors **46** and dielectric layer **48** are exposed at a front side **40F** of the passive device **40**. In the embodiment illustrated, the conductive vias **50** are not yet exposed at a back side **40B** of the passive device **40**, but will be exposed in subsequent processing.

[0036] Referring to FIG. **10**, the passive devices **40** are placed over one or more processing units of the processor device **10**. The passive devices **40** can be shared by some or all of the processing units **10A**, **10B**, **10C**, **10D**. In embodiments where the passive devices **40** are PMICs, they can be part of the power delivery network for the processor device **10**.

[0037] The processor device **10** and passive devices **40** are directly bonded in a face-to-face manner by hybrid bonding, such that the front side **10F** of the processor device **10** is bonded to the front sides **40F** of the passive devices **40**. Specifically, the dielectric layer **18** of the processor device **10** is bonded to the dielectric layers **28** of the passive devices **40** through dielectric-to-dielectric bonding, without using any adhesive material (e.g., die attach film), and a subset of the die connectors **16B** of the processor device **10** are bonded to the die connectors **46** of the passive devices **40** through metal-to-metal bonding, without using any eutectic material (e.g., solder). The hybrid bonding may be similar to the bonding of the processor device **10** and first memory devices **20**, described above. In some embodiments, the passive devices **40** and first memory devices **20** are simultaneously bonded to the processor device **10**.

[0038] The die connectors **46** of the passive devices **40** can have a large pitch. For example, the die connectors **46** can have a pitch in the range of about 9 μm to about 90 μm . The die connectors **16B** have the same pitch as the die connectors **46**. Forming the die connectors **16B** and **46** at a large pitch allows the connections between the processor device **10** and the first memory devices **20** to be formed at a low cost, which can be particularly advantageous when the passive devices **40** are devices with a low complexity such as PMICs.

[0039] In FIG. **3**, a dielectric layer **104** is formed surrounding the first memory devices **20** and passive devices **40**. The dielectric layer **104** can be formed after placement of the first memory devices **20** and passive devices **40** but before annealing to complete the hybrid bonding, or can be formed after annealing. The dielectric layer **104** fills gaps between the first memory devices **20** and passive devices **40**, thus protecting the semiconductor devices. The dielectric layer **104** may be an oxide such as silicon oxide, PSG, BSG, BPSG, or the like; a nitride such as silicon nitride or the like; a polymer such as polybenzoxazole (PBO), polyimide, benzocyclobuten (BCB), or the like; an encapsulant such as a molding compound, epoxy, or the like; the like, or a combination thereof. In some embodiments, the dielectric layer **104** is an oxide such as silicon oxide.

[0040] Conductive vias **106** are then formed to extend through the dielectric layer **104**. As an example to form the conductive vias **106**, openings are patterned in the dielectric layer **104**. The patterning may be by an acceptable process, such as by exposing the dielectric layer **104** to light when the dielectric layer **104** is a photo-sensitive material, or by etching the dielectric layer **104** using, for example, an anisotropic etch. The openings expose a subset of the die connectors **16C** of the processor device **10**. A seed layer is formed on the dielectric layer **104** and on portions of the die connectors **16C** exposed by the openings. In some embodiments, the seed layer is a metal layer, which may be a single layer or a composite layer comprising a plurality of sub-layers formed of different materials. In a particular embodiment, the seed layer comprises a titanium layer and a copper layer over the titanium layer. The seed layer may be formed using, for example, PVD or the

like. A conductive material is formed on the seed layer. The conductive material may be formed by plating, such as electroplating or electroless plating, or the like. The conductive material may comprise a metal, such as copper, titanium, tungsten, aluminum, or the like. Excess portions of the seed layer and conductive material are then removed, with the excess portions being portions overlying the dielectric layer **104**. The removal may be by a planarization process. The planarization process is performed on the seed layer, conductive material, dielectric layer **104**, first memory devices **20**, and passive devices **40**. The removal simultaneously removes excess portions of the seed layer and conductive material and exposes the conductive vias **30** and **50**. The planarization process may be, for example, a CMP process, a grinding process, an etch back process, the like, or combinations thereof. The remaining portions of the seed layer and conductive material in the openings form the conductive vias **106**. Top surfaces of the dielectric layer **104**, conductive vias **106**, semiconductor substrates **22** and **42**, and conductive vias **30** and **50** are planar after the planarization process.

[0041] In FIG. **4**, second memory devices **60** are bonded to the first memory devices **20** and the conductive vias **106**. The second memory devices **60** can be any acceptable memory devices, such as dynamic random access memory (DRAM) devices, static random access memory (SRAM) devices, resistive random-access memory (RRAM) devices, magnetoresistive random-access memory (MRAM) devices, phase-change random-access memory (PCRAM) devices, or the like.

[0042] Each second memory device **60** may be processed according to applicable manufacturing processes to form integrated circuits. For example, the second memory device **60** includes a semiconductor substrate **62**, an interconnect structure **64**, die connectors **66**, a dielectric layer **68**, and conductive vias **70** which, respectively, can be similar to the semiconductor substrate **12**, interconnect structure **14**, die connectors **16**, dielectric layer **18**, and conductive vias **30**. The die connectors **66** and dielectric layer **68** are exposed at a front side **60F** of the second memory device **60**. In the embodiment illustrated, the conductive vias **70** are not yet exposed at a back side **60B** of the second memory device **60**, but will be exposed in subsequent processing to form TSVs.

[0043] In some embodiments, the second memory devices **60** are memories for the processor device **10**. For example, the second memory devices **60** can be level 2 (L2) caches for the processor device **10**.

[0044] Referring to FIG. **10**, one of the second memory devices **60** is placed over each processing unit of the processor device **10**. Placing the second memory devices **60** directly over their corresponding processing units **10A**, **10B**, **10C**, **10D** allows the length of interconnections between logic devices and their corresponding memories to be reduced. The second memory devices **60** are electrically coupled to the processor device **10** by the conductive vias **106**, over which control signaling may be performed. Further, each of the second memory devices **60** are placed over the instruction cache device **201** and data cache device **20D** for their corresponding processing units **10A**, **10B**, **10C**, **10D**. The second memory devices **60** are connected to the first memory devices **20** by direct bonds, over which data signaling is performed. The direct bonds are shorter than the conductive vias **106**, and so the latency and power consumption of the interconnections between the memory devices may be improved.

[0045] The second memory devices **60** and first memory devices **20** are directly bonded in a face-to-back manner by hybrid bonding, such that the back sides **20B** of the first memory devices **20** are bonded to the front sides **60F** of the second memory devices **60**. Specifically, the semiconductor substrates **22** of the first memory devices **20** are bonded to the dielectric layers **68** of the second memory devices **60** through dielectric-to-dielectric bonding, without using any adhesive material (e.g., die attach film), and the conductive vias **30** of the first memory devices **20** are bonded to the die connectors **66** of the second memory devices **60** through metal-to-metal bonding, without using any eutectic material (e.g., solder). In some embodiments, an oxide, such as a native oxide, a thermal oxide, or the like, is formed at the back sides **20B** of the first memory devices **20**, such as on the semiconductor substrates **22**, and is used for the dielectric-to-dielectric bonding. The hybrid

bonding may be similar to the bonding of the processor device **10** and first memory devices **20**, described above.

[0046] The second memory devices **60** are wider than the first memory devices **20**, and so some portions of the conductive vias **106** and dielectric layer **104** also participating in the hybrid bonding. Specifically, the dielectric layers **68** of the second memory devices **60** are bonded to portions of the dielectric layer **104** through dielectric-to-dielectric bonding, without using any adhesive material (e.g., die attach film). Likewise, the die connectors **66** of the second memory devices **60** are bonded to the conductive vias **106** through metal-to-metal bonding, without using any eutectic material (e.g., solder).

[0047] The second memory devices **60** have active devices of a minimum feature size in the range of about 2 nm to about 65 nm. In some embodiments, the minimum feature size of the active devices of the second memory devices **60** is larger than the minimum feature size of the active devices of the first memory devices **20**. As such, the die connectors **66** of the second memory devices **60** can have a larger pitch than the die connectors **26** of the first memory devices **20**. For example, the die connectors **66** can have a pitch in the range of about 0.3 μm to about 90 μm . The conductive vias **30** and **106** have the same pitch as the die connectors **66**. Forming the die connectors **66** and the conductive vias **30** and **106** at a large pitch allows the connections between the first memory devices **20** and the second memory devices **60** to be formed at a low cost, which can be particularly advantageous when the second memory devices **60** are devices with a low complexity such as L2 cache.

[0048] In FIG. 5, a dielectric layer **108** is formed surrounding the second memory devices **60**. The dielectric layer **108** can be formed after placement of the second memory devices **60** but before annealing to complete the hybrid bonding, or can be formed after annealing. The dielectric layer **108** may be formed of a similar material and by a similar method as the dielectric layer **104**. In some embodiments, the dielectric layer **108** is an oxide such as silicon oxide. A planarization process is then performed on the dielectric layer **108** and second memory devices **60**. The planarization process may be, for example, a CMP process, a grinding process, an etch back process, the like, or combinations thereof. Top surfaces of the dielectric layer **108**, conductive vias **70**, and semiconductor substrates **62** are planar after the planarization process.

[0049] In FIG. 6, third memory devices **80** are bonded to the second memory devices **60**. The third memory devices **80** can be any acceptable memory devices, such as dynamic random access memory (DRAM) devices, static random access memory (SRAM) devices, resistive random-access memory (RRAM) devices, magnetoresistive random-access memory (MRAM) devices, phase-change random-access memory (PCRAM) devices, or the like.

[0050] Each third memory device **80** may be processed according to applicable manufacturing processes to form integrated circuits. For example, the third memory device **80** includes a semiconductor substrate **82**, an interconnect structure **84**, die connectors **86**, a dielectric layer **88**, and conductive vias **90** which, respectively, can be similar to the semiconductor substrate **12**, interconnect structure **14**, die connectors **16**, dielectric layer **18**, and conductive vias **70**. The die connectors **86** and dielectric layer **88** are exposed at a front side **80F** of the third memory device **80**. In the embodiment illustrated, the conductive vias **90** are not yet exposed at a back side **80B** of the third memory device **80**, but will be exposed in subsequent processing to form TSVs.

[0051] In some embodiments, the third memory devices **80** are memories for the processor device **10**. For example, the third memory devices **80** can be level 3 (L3) caches for the processor device **10**.

[0052] Referring to FIG. 10, the third memory devices **80** are placed over multiple processing units of the processor device **10**. The third memory devices **80** are thus shared by some or all of the processing units **10A**, **10B**, **10C**, **10D**. Placing the third memory devices **80** directly over their corresponding processing units **10A**, **10B**, **10C**, **10D** allows the length of interconnections between logic devices and their corresponding memories to be reduced. The third memory devices **80** are

electrically coupled to the processor device **10** through the second memory devices **60**, over which control signaling and data signaling are performed. The third memory devices **80** are connected to the second memory devices **60** by direct bonds. The direct bonds are shorter than conductive vias, and so the latency and power consumption of the interconnections between the memory devices may be improved.

[0053] The third memory devices **80** and second memory devices **60** are directly bonded in a face-to-back manner by hybrid bonding, such that the back sides **60B** of the second memory devices **60** are bonded to the front sides **80F** of the third memory devices **80**. Specifically, the semiconductor substrates **62** of the second memory devices **60** are bonded to the dielectric layers **88** of the third memory devices **80** through dielectric-to-dielectric bonding, without using any adhesive material (e.g., die attach film), and the conductive vias **70** of the second memory devices **60** are bonded to the die connectors **86** of the third memory devices **80** through metal-to-metal bonding, without using any eutectic material (e.g., solder). In some embodiments, an oxide, such as a native oxide, a thermal oxide, or the like, is formed at the back sides **60B** of the second memory devices **60**, such as on the semiconductor substrates **62**, and is used for the dielectric-to-dielectric bonding. The hybrid bonding may be similar to the bonding of the processor device **10** and first memory devices **20**, described above.

[0054] The third memory devices **80** are wider than the second memory devices **60** in some directions (see FIG. **10**), and so some portions of the dielectric layer **108** also participating in the hybrid bonding. Specifically, the dielectric layers **88** of the third memory devices **80** are bonded to portions of the dielectric layer **108** through dielectric-to-dielectric bonding, without using any adhesive material (e.g., die attach film).

[0055] The third memory devices **80** have active devices of a minimum feature size in the range of about 2 nm to about 65 nm. In some embodiments, the minimum feature size of the active devices of the third memory devices **80** is larger than the minimum feature size of the active devices of the second memory devices **60**. As such, the die connectors **86** of the third memory devices **80** can have a larger pitch than the pitch of the conductive vias **70** of the second memory devices **60**. For example, the die connectors **86** can have a pitch in the range of about 0.5 μm to about 90 μm . The conductive vias **70** have the same pitch as the die connectors **86**. Forming the die connectors **86** and the conductive vias **70** at a large pitch allows the connections between the second memory devices **60** and the third memory devices **80** to be formed at a low cost, which can be particularly advantageous when the third memory devices **80** are devices with a low complexity such as L3 cache.

[0056] In FIG. **7**, a dielectric layer **110** is formed surrounding the third memory devices **80**. The dielectric layer **110** can be formed after placement of the third memory devices **80** but before annealing to complete the hybrid bonding, or can be formed after annealing. The dielectric layer **110** may be formed of a similar material and by a similar method as the dielectric layer **104**. In some embodiments, the dielectric layer **110** is an oxide such as silicon oxide. A planarization process is then performed on the dielectric layer **110** and third memory devices **80**. The planarization process may be, for example, a CMP process, a grinding process, an etch back process, the like, or combinations thereof. Top surfaces of the dielectric layer **110**, conductive vias **90**, and semiconductor substrates **82** are planar after the planarization process.

[0057] Conductive vias **112** are then formed to extend through the dielectric layers **104**, **108**, **110**. The conductive vias **112** may be formed of a similar material and by a similar method as the conductive vias **106**. A first subset of the conductive vias **112A** extend through the dielectric layers **104**, **108**, **110**, and are connected to a subset of the die connectors **16D** of the processor device **10**. A second subset of the conductive vias **112B** extend through the dielectric layers **108**, **110**, and are connected to the conductive vias **50** of the passive devices **40**.

[0058] In FIG. **8**, a redistribution structure **114** is formed on the conductive vias **112**, the dielectric layer **110**, and the third memory devices **80**. The redistribution structure **114** includes multiple

metallization patterns among dielectric layers. For example, the redistribution structure **114** may be patterned as a plurality of discrete metallization patterns separated from each other by respective dielectric layers. In some embodiments, the dielectric layers are formed of a polymer, which may be a photo-sensitive material such as PBO, polyimide, BCB, or the like, may be patterned using a lithography mask. In other embodiments, the dielectric layers are formed of a nitride such as silicon nitride; an oxide such as silicon oxide, PSG, BSG, BPSG; or the like. The dielectric layers may be formed by spin coating, lamination, CVD, the like, or a combination thereof. After formation, the dielectric layers are patterned to expose underlying conductive features. For example, the bottom dielectric layer is patterned to expose portions of the conductive vias **90** and **112**, and intermediate dielectric layer(s) are patterned to expose portions of underlying metallization patterns. The patterning may be by an acceptable process, such as by exposing the dielectrics layers to light when the dielectric layers are a photo-sensitive material, or by etching using, for example, an anisotropic etch. If the dielectric layers are photo-sensitive materials, the dielectric layers can be developed after the exposure.

[0059] Metallization patterns are formed extending along and through each dielectric layer. A seed layer (not illustrated) is formed over each respective dielectric layer and in the openings through the respective dielectric layer. In some embodiments, the seed layer is a metal layer, which may be a single layer or a composite layer comprising a plurality of sub-layers formed of different materials. In some embodiments, the seed layer comprises a titanium layer and a copper layer over the titanium layer. The seed layer may be formed using a deposition process, such as PVD or the like. A photoresist is then formed and patterned on the seed layer. The photoresist may be formed by spin coating or the like and may be exposed to light for patterning. The pattern of the photoresist corresponds to the metallization pattern. The patterning forms openings through the photoresist to expose the seed layer. A conductive material is formed in the openings of the photoresist and on the exposed portions of the seed layer. The conductive material may be formed by plating, such as electroplating or electroless plating, or the like. The conductive material may comprise a metal or a metal alloy, such as copper, titanium, tungsten, aluminum, the like, or combinations thereof. Then, the photoresist and portions of the seed layer on which the conductive material is not formed are removed. The photoresist may be removed by an acceptable ashing or stripping process, such as using an oxygen plasma or the like. Once the photoresist is removed, exposed portions of the seed layer are removed, such as by using an acceptable etching process, such as by wet or dry etching. The remaining portions of the seed layer and conductive material form the metallization pattern for one layer of the redistribution structure **114**.

[0060] The redistribution structure **114** is illustrated as an example. More or fewer dielectric layers and metallization patterns than illustrated may be formed in the redistribution structure **114** by repeating or omitting the steps described above.

[0061] The metallization patterns of the redistribution structure **114** are connected to the conductive vias **112** and the back sides **80B** of the third memory devices **80** (e.g., to the conductive vias **90**). The metallization patterns of the redistribution structure **114** include power supply source (V.sub.DD) lines and power supply ground (V.sub.SS) lines, which are electrically coupled to the processor device **10** and passive devices **40** by the conductive vias **112** to form power delivery networks for the semiconductor devices in the integrated circuit package **100**. In embodiments where the passive devices **40** are PMICs, they can be part of the power delivery network for the processor device **10**. As noted above, the passive devices **40** are optional. For example, in some embodiments, the processor device **10** has built-in PMICs, and the passive devices **40** are omitted. The metallization patterns of the redistribution structure **114** also include data signal lines, which are electrically coupled to the processor device **10** by the conductive vias **112**. For example, some of the conductive vias **112** couple input/output (I/O) connections of the processor device **10** to the redistribution structure **114**. The processor device **10** may thus be coupled to external devices.

[0062] In FIG. **9**, a singulation process is performed by sawing along scribe line regions, e.g.,

around the device region **102A**. The singulation process includes sawing the wafer **102**, the dielectric layers **104**, **108**, **110**, and the redistribution structure **114**. The singulation process separates the device region **102A** (comprising the processor device **10**) from adjacent device regions (not illustrated) of the wafer **102** to form an integrated circuit package **100** comprising the processor device **10**. The first memory devices **20** are bonded to the processor device **10** in a face-to-face manner, the second memory devices **60** are bonded to the first memory devices **20** in a face-to-back manner, and the third memory devices **80** are bonded to the second memory devices **60** in a face-to-back manner, each without the use of solder. The resulting integrated circuit package **100** is thus free from solder. After singulation, the processor device **10**, the dielectric layers **104**, **108**, **110**, and the redistribution structure **114** are laterally coterminous.

[0063] FIG. **10** illustrates the electrical connections among the semiconductor devices of the resulting integrated circuit package **100**. Some features are omitted from FIG. **10** for clarity of illustration. A pair of first memory devices **20** (e.g., an instruction cache device **201** and a data cache device **20D**) are connected to each of the processing units **10A**, **10B**, **10C**, **10D** by direct bonds **118**. A second memory device **60** is connected to each pair of the first memory devices **20** by direct bonds **120**. A third memory device **80** is connected to multiple second memory devices **60** by direct bonds **122**. Passive devices **40** are optionally connected to the processing units **10A**, **10B**, **10C**, **10D** by direct bonds **124**. The second memory devices **60** are electrically coupled to the processor device **10** by the conductive vias **106**. The redistribution structure **114** is electrically coupled to the processor device **10** by the conductive vias **112A**, and is electrically coupled to the passive devices **40** by the conductive vias **112B**.

[0064] FIGS. **11** and **12** are cross-sectional views of intermediate steps during a process for forming a system implementing the integrated circuit package **100**, in accordance with some embodiments. FIGS. **11** and **12** are illustrated along reference cross-section X-X in FIG. **10**. In this embodiment, the integrated circuit package **100** is directly mounted to a package substrate.

[0065] In FIG. **11**, conductive connectors **116** are formed electrically coupled to the metallization patterns of the redistribution structure **114**. The conductive connectors **116** can be formed before or after the integrated circuit package **100** is singulated. The top dielectric layer of the redistribution structure **114** may be patterned to expose portions of the underlying metallization patterns. In some embodiments, under bump metallurgies (UBMs) may be formed in the openings. The conductive connectors **116** are formed on the UBMs. The conductive connectors **116** may be ball grid array (BGA) connectors, solder balls, metal pillars, controlled collapse chip connection (C4) bumps, micro bumps, electroless nickel-electroless palladium-immersion gold technique (ENEPIG) formed bumps, or the like. The conductive connectors **116** may be formed of a metal or metal alloy, such as solder, copper, aluminum, gold, nickel, silver, palladium, tin, the like, or a combination thereof. In some embodiments, the conductive connectors **116** are formed by initially forming a layer of solder through such commonly used methods such as evaporation, electroplating, printing, solder transfer, ball placement, or the like. Once a layer of solder has been formed on the structure, a reflow may be performed in order to shape the material into the desired bump shapes. In another embodiment, the conductive connectors **116** are metal pillars (such as a copper pillar) formed by a sputtering, printing, electro plating, electroless plating, CVD, or the like. The metal pillars may be solder free and have substantially vertical sidewalls. The conductive connectors **116** are electrically coupled to the metallization patterns of the redistribution structure **114**.

[0066] In FIG. **12**, the integrated circuit package **100** is flipped and attached to a package substrate **200** using the conductive connectors **116**. The package substrate **200** may be made of a semiconductor material such as silicon, germanium, diamond, or the like. Alternatively, compound materials such as silicon germanium, silicon carbide, gallium arsenic, indium arsenide, indium phosphide, silicon germanium carbide, gallium arsenic phosphide, gallium indium phosphide, combinations of these, and the like, may also be used. Additionally, the package substrate **200** may be a SOI substrate. Generally, an SOI substrate includes a layer of a semiconductor material such as

epitaxial silicon, germanium, silicon germanium, SOI, SGOI, or combinations thereof. The package substrate **200** is, in one alternative embodiment, based on an insulating core such as a fiberglass reinforced resin core. One example core material is fiberglass resin such as FR4. Alternatives for the core material include bismaleimide-triazine (BT) resin, or alternatively, other printed circuit board (PCB) materials or films. Build up films such as Ajinomoto build-up film (ABF) or other laminates may be used for package substrate **200**.

[0067] The package substrate **200** may include active and passive devices (not illustrated). Devices such as transistors, capacitors, resistors, combinations of these, and the like may be used to generate the structural and functional requirements of the design for the system. The devices may be formed using any suitable methods.

[0068] The package substrate **200** may also include metallization layers and vias (not illustrated) and bond pads **202** over the metallization layers and vias. The metallization layers may be formed over the active and passive devices and are designed to connect the various devices to form functional circuitry. The metallization layers may be formed of alternating layers of dielectric (e.g., low-k dielectric material) and conductive material (e.g., copper) with vias interconnecting the layers of conductive material and may be formed through any suitable process (such as deposition, damascene, dual damascene, or the like). In some embodiments, the package substrate **200** is substantially free of active and passive devices.

[0069] The conductive connectors **116** are reflowed to attach the UBMs of the redistribution structure **114** to the bond pads **202**. The conductive connectors **116** electrically and/or physically connect the package substrate **200**, including metallization layers in the package substrate **200**, to the integrated circuit package **100**. In some embodiments, passive devices (e.g., surface mount devices (SMDs), not illustrated) may be attached to the integrated circuit package **100** (e.g., bonded to the bond pads **202**) prior to mounting on the package substrate **200**. In such embodiments, the passive devices may be bonded to a same surface of the integrated circuit package **100** as the conductive connectors **116**. In some embodiments, passive devices (e.g., SMDs, not illustrated) may be attached to the package substrate **200**, e.g., to the bond pads **202**.

[0070] The conductive connectors **116** may have an epoxy flux (not illustrated) formed thereon before they are reflowed with at least some of the epoxy portion of the epoxy flux remaining after the integrated circuit package **100** is attached to the package substrate **200**. This remaining epoxy portion may act as an underfill to reduce stress and protect the joints resulting from the reflowing the conductive connectors **116**. In some embodiments, an underfill (not illustrated) may be formed between the integrated circuit package **100** and the package substrate **200**, surrounding the conductive connectors **116**. The underfill may be formed by a capillary flow process after the integrated circuit package **100** is attached or may be formed by a suitable deposition method before the integrated circuit package **100** is attached.

[0071] FIGS. **13** through **17** are cross-sectional views of intermediate steps during a process for forming a system implementing the integrated circuit package **100**, in accordance with some other embodiments. FIGS. **13** through **17** are illustrated along reference cross-section X-X in FIG. **10**. In this embodiment, the integrated circuit package **100** is singulated and included in a package component. Packaging of devices in one package region **302A** is illustrated, but it should be appreciated that any number of package regions may be simultaneously formed. The package region **302A** will be singulated in subsequent processing. The singulated package component may be a fan-out package, such as an integrated fan-out (InFO) package. The fan-out package is then mounted to a package substrate.

[0072] In FIG. **13**, a carrier substrate **302** is provided, and a release layer **304** is formed on the carrier substrate **302**. The carrier substrate **302** may be a glass carrier substrate, a ceramic carrier substrate, or the like. The carrier substrate **302** may be a wafer, such that multiple packages can be formed on the carrier substrate **302** simultaneously. The release layer **304** may be formed of a polymer-based material, which may be removed along with the carrier substrate **302** from the

overlying structures that will be formed in subsequent steps. In some embodiments, the release layer **304** is an epoxy-based thermal-release material, which loses its adhesive property when heated, such as a light-to-heat-conversion (LTHC) release coating. In other embodiments, the release layer **304** may be an ultra-violet (UV) glue, which loses its adhesive property when exposed to UV lights. The release layer **304** may be dispensed as a liquid and cured, may be a laminate film laminated onto the carrier substrate **302**, or may be the like. The top surface of the release layer **304** may be leveled and may have a high degree of planarity.

[0073] A redistribution structure **306** may be formed on the release layer **304**. The redistribution structure **306** can be formed in a similar manner and of similar materials as the redistribution structure **114** described with respect to FIG. **8**. The redistribution structure **306** includes dielectric layers and metallization patterns (sometimes referred to as redistribution layers or redistribution lines). More or fewer dielectric layers and metallization patterns than illustrated may be formed in the redistribution structure **306**. The redistribution structure **306** is optional. In some embodiments, a dielectric layer without metallization patterns is formed on the release layer **304** in lieu of the redistribution structure **306**.

[0074] In FIG. **14**, conductive vias **308** are formed extending through the topmost dielectric layer of the redistribution structure **306**. Thus, the conductive vias **308** are connected to the metallization patterns of the redistribution structure **306**. The conductive vias **308** are optional, and may be omitted. For example, the conductive vias **308** may (or may not) be omitted in embodiments where the redistribution structure **306** is omitted.

[0075] As an example to form the conductive vias **308**, openings can be formed in the topmost dielectric layer of the redistribution structure **306**. A seed layer is then formed over the redistribution structure **306**, e.g., on the topmost dielectric layer of the redistribution structure **306** and portions of the metallization pattern of the redistribution structure **306** exposed by the openings. In some embodiments, the seed layer is a metal layer, which may be a single layer or a composite layer comprising a plurality of sub-layers formed of different materials. In a particular embodiment, the seed layer comprises a titanium layer and a copper layer over the titanium layer. The seed layer may be formed using, for example, PVD or the like. A photoresist is formed and patterned on the seed layer. The photoresist may be formed by spin coating or the like and may be exposed to light for patterning. The pattern of the photoresist corresponds to conductive vias. The patterning forms openings through the photoresist to expose the seed layer. A conductive material is formed in the openings of the photoresist and on the exposed portions of the seed layer. The conductive material may be formed by plating, such as electroplating or electroless plating, or the like. The conductive material may comprise a metal, like copper, titanium, tungsten, aluminum, or the like. The photoresist and portions of the seed layer on which the conductive material is not formed are removed. The photoresist may be removed by an acceptable ashing or stripping process, such as using an oxygen plasma or the like. Once the photoresist is removed, exposed portions of the seed layer are removed, such as by using an acceptable etching process, such as by wet or dry etching. The remaining portions of the seed layer and conductive material form the conductive vias **308**.

[0076] A singulated integrated circuit package **100** is placed on the redistribution structure **306**. To form the singulated integrated circuit package **100**, an intermediate structure similar to that described with respect to FIG. **9** is obtained. As noted above, in the integrated circuit package **100**, the devices are bonded to one another without the use of solder. The singulated integrated circuit package **100** is thus free from solder.

[0077] In FIG. **15**, an encapsulant **310** is formed around the integrated circuit package **100**. The encapsulant **310** laterally surrounds the integrated circuit package **100**. The encapsulant **310** may be a molding compound, epoxy, or the like. The encapsulant **310** may be applied by compression molding, transfer molding, or the like, and may be applied in liquid or semi-liquid form and then subsequently cured.

[0078] In some embodiments, the encapsulant **310** is formed over the integrated circuit package **100** such that the redistribution structure **114** is buried or covered. A planarization process may be performed on the encapsulant **310** to expose the integrated circuit package **100**. The planarization process can remove material of the encapsulant **310** until the redistribution structure **114** is exposed. Top surfaces of the encapsulant **310** and redistribution structure **114** are coplanar after the planarization process. The planarization process may be, for example, a CMP process, a grinding process, an etch back process, the like, or combinations thereof. In other embodiments, the encapsulant **310** is not formed over the integrated circuit package **100**, and no planarization process is necessary to expose the integrated circuit package **100**.

[0079] A redistribution structure **312** is then formed on the encapsulant **310** and the redistribution structure **114**. The redistribution structure **312** can be formed in a similar manner and of similar materials as the redistribution structure **114** described with respect to FIG. **8**. The redistribution structure **312** includes dielectric layers and metallization patterns (sometimes referred to as redistribution layers or redistribution lines). More or fewer dielectric layers and metallization patterns than illustrated may be formed in the redistribution structure **306**. A bottom dielectric layer of the redistribution structure **312** physically contacts the encapsulant **310** and a top dielectric layer of the redistribution structure **114**. The metallization patterns of the redistribution structure **312** are electrically coupled to the metallization patterns of the redistribution structure **114**.

[0080] Conductive connectors **314** are formed physically and electrically connected to the metallization patterns of the redistribution structure **312**. The conductive connectors **314** can be formed in a similar manner and of similar materials as the conductive connectors **116** described with respect to FIG. **11**.

[0081] In FIG. **16**, a carrier substrate debonding is performed to detach (de-bond) the carrier substrate **302** from the redistribution structure **306**, e.g., the bottommost dielectric layer of the redistribution structure **306**. In accordance with some embodiments, the de-bonding includes projecting a light such as a laser light or an UV light on the release layer **304** so that the release layer **304** decomposes under the heat of the light and the carrier substrate **302** can be removed. The structure can then be flipped over and placed on, e.g., a tape.

[0082] Further, conductive connectors **316** are formed through the bottommost dielectric layer of the redistribution structure **306**. Openings can be formed through the bottommost dielectric layer of the redistribution structure **306**, exposing portions of the metallization patterns of the redistribution structure **306**. The openings may be formed, for example, using laser drilling, etching, or the like. The conductive connectors **316** are formed in the openings, and are connected to exposed portions of the metallization patterns of the redistribution structure **306**. The conductive connectors **316** can be formed in a similar manner and of similar materials as the conductive connectors **116** described with respect to FIG. **11**.

[0083] In FIG. **17**, a singulation process is performed by sawing along scribe line regions, e.g., around the package region **302A**. The singulation process includes sawing the redistribution structures **306**, **312** and encapsulant **310**. The singulation process separates the package region **302A** from adjacent package regions (not illustrated) to form an integrated circuit package **300**. After singulation, the redistribution structures **306**, **312** and the encapsulant **310** are laterally coterminous.

[0084] Another integrated circuit package **400** can be attached to the integrated circuit package **300** to form a package-on-package structure. The integrated circuit package **400** may be a memory package. The integrated circuit package **400** can be attached to the integrated circuit package **300** before or after the integrated circuit package **300** is singulated. The integrated circuit package **400** includes a substrate **402** and one or more dies **404** connected to the substrate **402**. In some embodiments (not shown) one or more stacks of dies **404** are connected to the substrate **402**. The substrate **402** may be made of a semiconductor material such as silicon, germanium, diamond, or the like. In some embodiments, compound materials such as silicon germanium, silicon carbide,

gallium arsenic, indium arsenide, indium phosphide, silicon germanium carbide, gallium arsenic phosphide, gallium indium phosphide, combinations of these, and the like, may also be used. Additionally, the substrate **402** may be a silicon-on-insulator (SOI) substrate. Generally, an SOI substrate includes a layer of a semiconductor material such as epitaxial silicon, germanium, silicon germanium, SOI, silicon germanium on insulator (SGOI), or combinations thereof. The substrate **402** is, in one alternative embodiment, based on an insulating core such as a fiberglass reinforced resin core. One example core material is fiberglass resin such as FR4. Alternatives for the core material include bismaleimide-triazine (BT) resin, or alternatively, other printed circuit board (PCB) materials or films. Build up films such as Ajinomoto build-up film (ABF) or other laminates may be used for substrate **402**.

[0085] The substrate **402** may include active and passive devices (not shown). As one of ordinary skill in the art will recognize, a wide variety of devices such as transistors, capacitors, resistors, combinations of these, and the like may be used to generate the structural and functional requirements of the design for the integrated circuit package **400**. The devices may be formed using any suitable methods. The substrate **402** may also include metallization layers (not shown) and through vias. The metallization layers may be formed over the active and passive devices and are designed to connect the various devices to form functional circuitry. The metallization layers may be formed of alternating layers of dielectric (e.g., low-k dielectric material) and conductive material (e.g., copper) with vias interconnecting the layers of conductive material and may be formed through any suitable process (such as deposition, damascene, dual damascene, or the like). In some embodiments, the substrate **402** is substantially free of active and passive devices.

[0086] The substrate **402** may have bond pads **406** on a side the substrate **402**, to connect to the conductive connectors **316**. In some embodiments, the bond pads **406** are formed by forming recesses (not shown) into dielectric layers (not shown) on the side of the substrate **402**. The recesses may be formed to allow the bond pads **406** to be embedded into the dielectric layers. In other embodiments, the recesses are omitted as the bond pads **406** may be formed on the dielectric layer. In some embodiments, the bond pads **406** include a thin seed layer (not shown) made of copper, titanium, nickel, gold, palladium, the like, or a combination thereof. The conductive material of the bond pads **406** may be deposited over the thin seed layer. The conductive material may be formed by an electro-chemical plating process, an electroless plating process, CVD, ALD, PVD, the like, or a combination thereof. In an embodiment, the conductive material of the bond pads **406** is copper, tungsten, aluminum, silver, gold, the like, or a combination thereof.

[0087] In an embodiment, the bond pads **406** are UBMs that include three layers of conductive materials, such as a layer of titanium, a layer of copper, and a layer of nickel. For example, the bond pads **406** may be formed from copper, may be formed on a layer of titanium (not shown), and have a nickel finish, which may improve the shelf life of the integrated circuit package **400**, which may be particularly advantageous when the integrated circuit package **400** is a memory device such as a DRAM module. However, one of ordinary skill in the art will recognize that there are many suitable arrangements of materials and layers, such as an arrangement of chrome/chrome-copper alloy/copper/gold, an arrangement of titanium/titanium tungsten/copper, or an arrangement of copper/nickel/gold, that are suitable for the formation of the bond pads **406**. Any suitable materials or layers of material that may be used for the bond pads **406** are fully intended to be included within the scope of the current application.

[0088] In the illustrated embodiment, the dies **404** are connected to the substrate **402** by conductive bumps, although other connections may be used, such as wire bonds. In an embodiment, the dies **404** are stacked memory dies. For example, the dies **404** may be memory dies such as low-power (LP) double data rate (DDR) memory modules, such as LPDDR1, LPDDR2, LPDDR3, LPDDR4, or the like.

[0089] The dies **404** and the wire bonds (when present) may be encapsulated by a molding material **410**. The molding material **410** may be molded on the dies **404** and the wire bonds, for example,

using compression molding. In some embodiments, the molding material **410** is a molding compound, a polymer, an epoxy, silicon oxide filler material, the like, or a combination thereof. A curing process may be performed to cure the molding material **410**; the curing process may be a thermal curing, a UV curing, the like, or a combination thereof. In some embodiments, the dies **404** are buried in the molding material **410**, and after the curing of the molding material **410**, a planarization step, such as a grinding, is performed to remove excess portions of the molding material **410** and provide a substantially planar surface for the integrated circuit package **400**. [0090] After the integrated circuit package **400** is formed, the integrated circuit package **400** is attached to the integrated circuit package **300** by way of the conductive connectors **316**. The conductive connectors **316** can be connected to the bond pads **406** by reflowing the conductive connectors **316**. The dies **404** may thus be electrically coupled to the integrated circuit package **100** through the conductive connectors **316**, the conductive vias **308**, and the redistribution structures **306**, **312**.

[0091] In some embodiments, a solder resist (not shown) is formed on the side of the substrate **402** opposing the dies **404**. The conductive connectors **316** may be disposed in openings in the solder resist to be connected to conductive features (e.g., the bond pads **406**) in the substrate **402**. The solder resist may be used to protect areas of the substrate **402** from external damage.

[0092] In some embodiments, the conductive connectors **316** have an epoxy flux (not shown) formed thereon before they are reflowed with at least some of the epoxy portion of the epoxy flux remaining after the integrated circuit package **400** is attached to the redistribution structure **306**.

[0093] In some embodiments, an underfill (not shown) is formed between the redistribution structure **306** and the substrate **402**, and surrounding the conductive connectors **316**. The underfill may reduce stress and protect the joints resulting from the reflowing of the conductive connectors **316**. The underfill may be formed by a capillary flow process after the integrated circuit package **400** is attached or may be formed by a suitable deposition method before the integrated circuit package **400** is attached. In embodiments where the epoxy flux is formed, it may act as the underfill.

[0094] The package-on-package structure is then flipped and attached to a package substrate **200** using the conductive connectors **314**. The package substrate **200** may be similar to the package substrate **200** described with respect to FIG. 12. For example, the package substrate **200** can include bond pads **202**, which are connected to the conductive connectors **314**.

[0095] FIGS. 18 through 24 are various views of intermediate steps during a process for forming an integrated circuit package **500**, in accordance with some other embodiments. FIGS. 18 through 23 are cross-sectional views of the integrated circuit package **500**, and FIG. 24 is a three-dimensional diagram illustrating electrical connections among the semiconductor devices of the integrated circuit package **500**, where the cross-sectional views are illustrated along reference cross-section X-X in FIG. 24. Some features are omitted from FIG. 24 for clarity of illustration. In this embodiment, some of the memory devices are combined so that a single memory device can be used to provide both L2 and L3 caches for a processing unit. The quantity of device layers in the integrated circuit package **500** may thus be reduced.

[0096] In FIG. 18, a wafer **102** is obtained. The wafer **102** is similar to that discussed with respect to FIG. 1, and comprises a processor device **10** in the device region **102A**.

[0097] First memory devices **20** are then bonded to the processor device **10** (e.g., the wafer **102**). The first memory devices **20** are similar to those discussed with respect to FIG. 2, and can be L1 caches for the processor device **10**. Referring to FIG. 24, two of the first memory devices **20**, such as an instruction cache device **20I** (e.g., a L1i cache) and a data cache device **20D** (e.g., a L1d cache), can be bonded to each of the processing units **10A**, **10B**, **10C**, **10D** of the processor device **10**.

[0098] The processor device **10** and first memory devices **20** are directly bonded in a face-to-face manner by hybrid bonding, such that the front side **10F** of the processor device **10** is bonded to the

front sides **20F** of the first memory devices **20**. Specifically, the dielectric layer **18** of the processor device **10** is bonded to the dielectric layers **28** of the first memory devices **20** through dielectric-to-dielectric bonding, without using any adhesive material (e.g., die attach film), and a subset of the die connectors **16A** of the processor device **10** are bonded to the die connectors **26** of the first memory devices **20** through metal-to-metal bonding, without using any eutectic material (e.g., solder).

[0099] Optionally, passive devices **40** are also bonded to the processor device **10** (e.g., the wafer **102**). The passive devices **40** are similar to those discussed with respect to FIG. 2, and can be part of the power delivery network for the processor device **10**. Referring to FIG. 24, the passive devices **40** can be shared by some or all of the processing units **10A**, **10B**, **10C**, **10D** of the processor device **10**.

[0100] The processor device **10** and passive devices **40** are directly bonded in a face-to-face manner by hybrid bonding, such that the front side **10F** of the processor device **10** is bonded to the front sides **40F** of the passive devices **40**. Specifically, the dielectric layer **18** of the processor device **10** is bonded to the dielectric layers **28** of the passive devices **40** through dielectric-to-dielectric bonding, without using any adhesive material (e.g., die attach film), and a subset of the die connectors **16B** of the processor device **10** are bonded to the die connectors **46** of the passive devices **40** through metal-to-metal bonding, without using any eutectic material (e.g., solder).

[0101] In FIG. 19, a dielectric layer **104** is formed surrounding the first memory devices **20** and passive devices **40**. The dielectric layer **104** is similar to that discussed with respect to FIG. 3, and can be formed in a similar manner. Conductive vias **106** are then formed to extend through the dielectric layer **104**. The conductive vias **106** are similar to those discussed with respect to FIG. 3, and can be formed in a similar manner. The conductive vias **106** are connected to a subset of the die connectors **16C** of the processor device **10**. A planarization process is performed to expose the conductive vias **30** and **50**.

[0102] In FIG. 20, combination memory devices **510** are bonded to the first memory devices **20** and the conductive vias **106**. The combination memory devices **510** provide multiple types of memories for the processor device **10**. For example, the combination memory devices **510** can be both L2 and L3 caches for the processor device **10**.

[0103] Each combination memory device **510** may be processed according to applicable manufacturing processes to form integrated circuits. For example, the combination memory device **510** includes a semiconductor substrate **512**. The semiconductor substrate **512** can be similar to the semiconductor substrate **12** (see FIG. 2), but includes two memory regions **512A**, **512B**. The memory regions **512A**, **512B** include the different types of memory, such as L2 and L3 caches, respectively. The combination memory device **510** further includes an interconnect structure **514**, die connectors **516**, a dielectric layer **518**, and conductive vias **520** which, respectively, can be similar to the interconnect structure **14**, die connectors **16**, dielectric layer **18**, and conductive vias **30** (see FIG. 2). The die connectors **516** and dielectric layer **518** are exposed at a front side **510F** of the combination memory device **510**. In the embodiment illustrated, the conductive vias **520** are not yet exposed at a back side **510B** of the combination memory device **510**, but will be exposed in subsequent processing to form TSVs.

[0104] The processor device **10** and combination memory devices **510** are directly bonded in a face-to-back manner by hybrid bonding, such that the back sides **20B** of the first memory devices **20** are bonded to the front sides **510F** of the combination memory devices **510**. Specifically, the semiconductor substrates **22** of the first memory devices **20** are bonded to the dielectric layers **518** of the combination memory devices **510** through dielectric-to-dielectric bonding, without using any adhesive material (e.g., die attach film), and the conductive vias **30** of the first memory devices **20** are bonded to the die connectors **516** of the combination memory devices **510** through metal-to-metal bonding, without using any eutectic material (e.g., solder). Some portions of the conductive vias **106** and dielectric layer **104** also participating in the hybrid bonding. Specifically, the

dielectric layers **518** of the combination memory devices **510** are bonded to portions of the dielectric layer **104** through dielectric-to-dielectric bonding, without using any adhesive material (e.g., die attach film). Likewise, the die connectors **516** of the combination memory devices **510** are bonded to the conductive vias **106** through metal-to-metal bonding, without using any eutectic material (e.g., solder).

[0105] Referring to FIG. **24**, the combination memory devices **510** can be shared by some or all of the processing units **10A**, **10B**, **10C**, **10D** of the processor device **10**. The combination memory devices **510** each include a plurality of memory regions **512A** and a memory region **512B**. Specifically, the combination memory device **510** includes a memory region **512A** for each processing unit it is bonded to. In the embodiment shown, each combination memory device **510** is bonded to two processing units and thus includes two memory regions **512A**. As noted above, the memory regions **512A** can include L2 caches and the memory region **512B** can include a L3 cache. The memory region **512B** of each combination memory device **510** can be electrically coupled to the memory regions **512A** of the combination memory device by the interconnect structure **514**. The combination memory devices **510** are electrically coupled to the processor device **10** by the conductive vias **106**, over which control signaling may be performed. The combination memory devices **510** are also connected to the first memory devices **20** by direct bonds, over which data signaling is performed.

[0106] The combination memory devices **510** have active devices of a minimum feature size in the range of about 2 nm to about 65 nm. In some embodiments, the minimum feature size of the active devices of the combination memory devices **510** is larger than the minimum feature size of the active devices of the first memory devices **20**. As such, the die connectors **516** of the combination memory devices **510** can have a larger pitch than the pitch of the die connectors **26** of the first memory devices **20**. For example, the die connectors **516** can have a pitch in the range of about 0.3 μm to about 90 μm . The conductive vias **30** and **106** have the same pitch as the die connectors **516**. Forming the die connectors **516** and the conductive vias **30** and **106** at a large pitch allows the connections between the first memory devices **20** and the combination memory devices **510** to be formed at a low cost, which can be particularly advantageous when the combination memory devices **510** are devices with a low complexity such as L2/L3 caches.

[0107] In FIG. **21**, a dielectric layer **108** is formed surrounding the combination memory devices **510**. The dielectric layer **108** is similar to that discussed with respect to FIG. **5**, and can be formed in a similar manner. Conductive vias **112** are then formed to extend through the dielectric layers **104**, **108**. The conductive vias **112** are similar to those discussed with respect to FIG. **7**, and can be formed in a similar manner. A first subset of the conductive vias **112A** extend through the dielectric layers **104**, **108**, and are connected to a subset of the die connectors **16D** of the processor device **10**. A second subset of the conductive vias **112B** extend through the dielectric layer **108**, and are connected to the conductive vias **50** of the passive devices **40**. A planarization process is performed to expose the conductive vias **520**.

[0108] In FIG. **22**, a redistribution structure **114** is formed on the conductive vias **112**, the dielectric layer **108**, and the combination memory devices **510**. The redistribution structure **114** is similar to that discussed with respect to FIG. **8**, and can be formed in a similar manner. The metallization patterns of the redistribution structure **114** are connected to the conductive vias **112** and the back sides **510B** of the combination memory devices **510** (e.g., to the conductive vias **520**). The metallization patterns of the redistribution structure **114** include power supply source (V.sub.DD) lines and power supply ground (V.sub.SS) lines, which are electrically coupled to the processor device **10** and passive devices **40** by the conductive vias **112** to form power delivery networks for the semiconductor devices in the integrated circuit package **500**.

[0109] In FIG. **23**, a singulation process is performed by sawing along scribe line regions, e.g., around the device region **102A**. The singulation process is similar to that discussed with respect to FIG. **9**. After singulation, the processor device **10**, the dielectric layers **104**, **108**, and the

redistribution structure **114** are laterally coterminous.

[0110] FIG. **24** illustrates the electrical connections among the semiconductor devices of the resulting integrated circuit package **500**. Some features are omitted from FIG. **24** for clarity of illustration. A pair of first memory devices **20** (e.g., an instruction cache device **201** and a data cache device **20D**) are connected to each of the processing units **10A**, **10B**, **10C**, **10D** by direct bonds **530**. Combination memory devices **510** are connected to the first memory devices **20** by direct bonds **532**. Passive devices **40** are optionally connected to the processing units **10A**, **10B**, **10C**, **10D** by direct bonds **534**. The redistribution structure **114** is electrically coupled to the processor device **10** by the conductive vias **112A**, and is electrically coupled to the passive devices **40** by the conductive vias **112B**.

[0111] After the integrated circuit package **500** is formed, it can be implemented in systems similar to those discussed with respect to FIGS. **12** and **17**. In some embodiments, the integrated circuit package **500** is directly mounted to a package substrate **200** (see FIG. **25**). In some embodiments, the integrated circuit package **500** is singulated and included in a package component, which is mounted to a package substrate **200** (see FIG. **26**).

[0112] FIGS. **27** through **31** are various views of intermediate steps during a process for forming an integrated circuit package **600**, in accordance with some other embodiments. FIGS. **27** through **30** are cross-sectional views of the integrated circuit package **600**, and FIG. **31** is a three-dimensional diagram illustrating electrical connections among the semiconductor devices of the integrated circuit package **600**, where the cross-sectional views are illustrated along reference cross-section X-X in FIG. **31**. Some features are omitted from FIG. **31** for clarity of illustration. In this embodiment, some of the memory devices are combined so that a single memory device can be used to provide L1, L2, and L3 caches for a processing unit. The quantity of device layers in the integrated circuit package **600** may thus be further reduced.

[0113] In FIG. **27**, a wafer **102** is obtained. The wafer **102** is similar to that discussed with respect to FIG. **1**, and comprises a processor device **10** in the device region **102A**. A combination memory device **610** is then bonded to the processor device **10** (e.g., the wafer **102**). The combination memory device **610** provides multiple types of memories for the processor device **10**. For example, the combination memory device **610** can be L1, L2, and L3 caches for the processor device **10**.

[0114] The combination memory device **610** may be processed according to applicable manufacturing processes to form integrated circuits. For example, the combination memory device **610** includes a semiconductor substrate **612**. The semiconductor substrate **612** can be similar to the semiconductor substrate **12** (see FIG. **2**), but includes three memory regions **612A**, **612B**, **612C**. The memory regions **612A**, **612B**, **612C** include different types of memory, such as L1, L2, and L3 caches, respectively. The combination memory device **610** further includes an interconnect structure **614**, die connectors **616**, a dielectric layer **618**, and conductive vias **620** which, respectively, can be similar to the interconnect structure **14**, die connectors **16**, dielectric layer **18**, and conductive vias **30** (see FIG. **2**). The die connectors **616** and dielectric layer **618** are exposed at a front side **610F** of the combination memory device **610**. In the embodiment illustrated, the conductive vias **620** are not yet exposed at a back side **610B** of the combination memory device **610**, but will be exposed in subsequent processing to form TSVs.

[0115] Referring to FIG. **31**, the combination memory device **610** is shared by all of the processing units **10A**, **10B**, **10C**, **10D** of the processor device **10**. The combination memory device **610** includes two memory region **612A** (such as an instruction cache region (e.g., a L1i cache) and a data cache region (e.g., a L1d cache)) and one memory region **612B** (such as a L2 cache) for each processing unit it is bonded to. The combination memory device **610** further includes one memory region **612C** (such as an L3 cache) that is shared by all processing units. In the embodiment shown, the combination memory device **610** is bonded to four processing units, and thus includes eight memory regions **612A**, four memory regions **612B**, and one memory region **612C**. The memory regions **612A**, **612B**, **612C** of the combination memory device **610** are electrically coupled by the

interconnect structure **614**. The combination memory device **610** is connected to the processor device **10** by direct bonds, over which control signaling and data signaling is performed.

[0116] The processor device **10** and combination memory device **610** are directly bonded in a face-to-face manner by hybrid bonding, such that the front side **10F** of the processor device **10** is bonded to the front side **610F** of the combination memory device **610**. Specifically, the dielectric layer **18** of the processor device **10** is bonded to the dielectric layer **628** of the combination memory device **610** through dielectric-to-dielectric bonding, without using any adhesive material (e.g., die attach film), and the die connectors **16** of the processor device **10** are bonded to the die connectors **626** of the combination memory device **610** through metal-to-metal bonding, without using any eutectic material (e.g., solder).

[0117] The combination memory device **610** have active devices of a minimum feature size in the range of about 2 nm to about 65 nm. As noted above, the combination memory device **610** has multiple types of memories. As such, the die connectors **616** of the combination memory device **610** can be grouped into several subsets that have different pitches. For example, a first subset of the die connectors **616A** can have a pitch in the range of about 0.05 μm to about 10 μm , and can be electrically coupled to the memory regions **612A** of the combination memory device **610**.

Likewise, a second subset of the die connectors **616B** can have a pitch in the range of about 0.3 μm to about 90 μm , and can be electrically coupled to the memory regions **612B** of the combination memory device **610**. Further, a third subset of the die connectors **616C** can have a pitch in the range of about 0.5 μm to about 90 μm , and can be electrically coupled to the memory region **612C** of the combination memory device **610**. The pitch of the die connectors **616C** is greater than the pitch of the die connectors **616B**, and the pitch of the die connectors **616B** is greater than the pitch of the die connectors **616A**. The die connectors **16** of processor device **10** have the same pitch as the corresponding die connectors **616** of the combination memory device **610**. Specifically, a first subset of the die connectors **16A** have the same pitch as the die connectors **616A**, a second subset of the die connectors **16B** have the same pitch as the die connectors **616B**, and a third subset of the die connectors **16C** have the same pitch as the die connectors **616C**. Forming the die connectors **16** and **616** with varying pitches allows a single memory device to accommodate multiple types of memory, thus reducing the amount of dies included in the integrated circuit package **600** and allowing the integrated circuit package **600** to be formed at a low cost.

[0118] Optionally, passive devices **40** (see FIG. 31) are also bonded to the processor device **10** (e.g., the wafer **102**). The passive devices **40** are similar to those discussed with respect to FIG. 2, and can be part of the power delivery network for the processor device **10**. Referring to FIG. 31, the passive devices **40** can be shared by some or all of the processing units **10A**, **10B**, **10C**, **10D** of the processor device **10**. The processor device **10** and passive devices **40** are directly bonded in a face-to-face manner by hybrid bonding, in a similar manner as that discussed above with respect to FIG. 2.

[0119] In FIG. 28, a dielectric layer **104** is formed surrounding the combination memory device **610** and passive devices **40** (see FIG. 31). The dielectric layer **104** is similar to that discussed with respect to FIG. 3, and can be formed in a similar manner. Conductive vias **112** are then formed to extend through the dielectric layer **104**. The conductive vias **112** are similar to those discussed with respect to FIG. 7, and can be formed in a similar manner. The conductive vias **112** are connected to a subset of the die connectors **16D** of the processor device **10**. A planarization process is performed to expose the conductive vias **620**.

[0120] In FIG. 29, a redistribution structure **114** is formed on the conductive vias **112**, the dielectric layer **104**, and the combination memory device **610**. The redistribution structure **114** is similar to that discussed with respect to FIG. 8, and can be formed in a similar manner. The metallization patterns of the redistribution structure **114** are connected to the conductive vias **112** and the back sides **610B** of the combination memory device **610** (e.g., to the conductive vias **620**). The metallization patterns of the redistribution structure **114** include power supply source (V.sub.DD)

lines and power supply ground (V.sub.SS) lines, which are electrically coupled to the processor device **10** and passive devices **40** to form power delivery networks for the semiconductor devices in the integrated circuit package **600**. The metallization patterns of the redistribution structure **114** are electrically coupled to the processor device **10** by the conductive vias **112**, and are electrically coupled to the passive devices **40** by the conductive vias **50**. Conductive connectors **116** are then formed electrically coupled to the metallization patterns of the redistribution structure **114**. The conductive connectors **116** are similar to those discussed with respect to FIG. **8**, and can be formed in a similar manner.

[0121] In FIG. **30**, a singulation process is performed by sawing along scribe line regions, e.g., around the device region **102A**. The singulation process is similar to that discussed with respect to FIG. **9**. After singulation, the processor device **10**, the dielectric layer **104**, and the redistribution structure **114** are laterally coterminous.

[0122] FIG. **31** illustrates the electrical connections among the semiconductor devices of the resulting integrated circuit package **600**. Some features are omitted from FIG. **31** for clarity of illustration. The combination memory device **610** is connected to the processing units **10A**, **10B**, **10C**, **10D** by direct bonds **630**. Passive devices **40** are optionally connected to the processing units **10A**, **10B**, **10C**, **10D** by direct bonds **632**. The redistribution structure **114** is electrically coupled to the processor device **10** by the conductive vias **112**.

[0123] After the integrated circuit package **600** is formed, it can be implemented in systems similar to those discussed with respect to FIGS. **12** and **17**. In some embodiments, the integrated circuit package **600** is directly mounted to a package substrate **200** (see FIG. **32**). In some embodiments, the integrated circuit package **600** is singulated and included in a package component, which is mounted to a package substrate **200** (see FIG. **33**).

[0124] Embodiments may achieve advantages. Stacking memory devices on a processor device instead of including memories with the processor device may allow the overall amount of memory in an integrated circuit package to be increased without substantially increasing manufacturing costs of the processor device. Further, forming a processor device without memories allows more processing units (e.g., cores) to be included in the processor device without substantially increasing the footprint of the processor device. Connecting the processor device and memory devices by hybrid bonding allows the connections between the devices to be shorter than traditional interconnects. The latency of data signaling and the interconnection bandwidth between the processor device and memory devices may thus be improved. Further, the impedance and thus power consumption of the connections may also be reduced.

[0125] Other features and processes may also be included. For example, testing structures may be included to aid in the verification testing of the 3D packaging or 3DIC devices. The testing structures may include, for example, test pads formed in a redistribution layer or on a substrate that allows the testing of the 3D packaging or 3DIC, the use of probes and/or probe cards, and the like. The verification testing may be performed on intermediate structures as well as the final structure. Additionally, the structures and methods disclosed herein may be used in conjunction with testing methodologies that incorporate intermediate verification of known good dies to increase the yield and decrease costs.

[0126] In an embodiment, a structure includes: a processor device including logic devices and being free from memories; a first memory device directly face-to-face bonded to the processor device by metal-to-metal bonds and by dielectric-to-dielectric bonds; a first dielectric layer laterally surrounding the first memory device; a redistribution structure over the first dielectric layer and the first memory device, the redistribution structure including metallization patterns; and first conductive vias extending through the first dielectric layer, the first conductive vias connecting the metallization patterns of the redistribution structure to the processor device.

[0127] In some embodiments of the structure, the metallization patterns of the redistribution structure are connected to the first memory device. In some embodiments, the structure further

includes: a passive device directly face-to-face bonded to the processor device by metal-to-metal bonds and by dielectric-to-dielectric bonds, the first dielectric layer laterally surrounding the passive device, the metallization patterns of the redistribution structure connected to the passive device. In some embodiments, the structure further includes: a second memory device directly face-to-back bonded to the first memory device by metal-to-metal bonds and by dielectric-to-dielectric bonds, the metallization patterns of the redistribution structure connected to the second memory device; second conductive vias extending through the first dielectric layer, the second conductive vias connecting the second memory device to the processor device; and a second dielectric layer laterally surrounding the second memory device, the first conductive vias extending through the second dielectric layer. In some embodiments, the structure further includes: a passive device directly face-to-face bonded to the processor device by metal-to-metal bonds and by dielectric-to-dielectric bonds, the first dielectric layer laterally surrounding the passive device; and third conductive vias extending through the second dielectric layer, the third conductive vias connecting the redistribution structure to the passive device. In some embodiments, the structure further includes: a second memory device directly face-to-back bonded to the first memory device by metal-to-metal bonds and by dielectric-to-dielectric bonds; second conductive vias extending through the first dielectric layer, the second conductive vias connecting the second memory device to the processor device; a second dielectric layer laterally surrounding the second memory device, the first conductive vias extending through the second dielectric layer; a third memory device directly face-to-back bonded to the second memory device by metal-to-metal bonds and by dielectric-to-dielectric bonds, the redistribution structure connected to the third memory device; and a third dielectric layer laterally surrounding the third memory device, the first conductive vias extending through the third dielectric layer. In some embodiments, the structure further includes: a passive device directly face-to-face bonded to the processor device by metal-to-metal bonds and by dielectric-to-dielectric bonds, the first dielectric layer laterally surrounding the passive device; and third conductive vias extending through the second dielectric layer and the third dielectric layer, the third conductive vias connecting the redistribution structure to the passive device. In some embodiments, the structure further includes: a package substrate; and conductive connectors connecting the package substrate to the redistribution structure.

[0128] In an embodiment, a structure includes: a processor device having a front side; a first memory device having a front side and a back side opposite the front side, the front side of the first memory device connected to the front side of the processor device by metal-to-metal bonds and by dielectric-to-dielectric bonds; a first dielectric layer laterally surrounding the first memory device; first conductive vias extending through the first dielectric layer, the first conductive vias connected to the front side of the processor device; a second memory device having a front side and a back side opposite the front side, the front side of the second memory device connected to the first conductive vias and the back side of the first memory device by metal-to-metal bonds, the front side of the second memory device connected to the first dielectric layer and the back side of the first memory device by dielectric-to-dielectric bonds, the first memory device being a different type of memory device than the second memory device; and a second dielectric layer laterally surrounding the second memory device.

[0129] In some embodiments, the structure further includes: a third memory device having a front side and a back side opposite the front side, the front side of the third memory device connected to the second dielectric layer and the back side of the second memory device by dielectric-to-dielectric bonds, the front side of the third memory device connected to the back side of the second memory device by metal-to-metal bonds; a third dielectric layer laterally surrounding the third memory device; second conductive vias extending through the first dielectric layer, the second dielectric layer, and the third dielectric layer, the second conductive vias connected to the front side of the processor device; and a redistribution structure connected to the second conductive vias and the back side of the third memory device. In some embodiments of the structure, the first memory

device is a level 1 (L1) cache for the processor device, the second memory device is a level 2 (L2) cache for the processor device, and the third memory device is a level 3 (L3) cache for the processor device. In some embodiments, the structure further includes: second conductive vias extending through the first dielectric layer and the second dielectric layer, the second conductive vias connected to the front side of the processor device; and a redistribution structure connected to the second conductive vias and the back side of the second memory device. In some embodiments of the structure, the first memory device is a level 1 (L1) cache for the processor device, and the second memory device is both a level 2 (L2) cache and a level 3 (L3) cache for the processor device. In some embodiments of the structure, the processor device includes a plurality of processing units, and the structure further includes: first memory devices, the first memory device being one of the first memory devices, respective pairs of the first memory devices being connected to respective ones of the processing units of the processor device; and second memory devices, the second memory device being one of the second memory devices, respective ones of the second memory devices being connected to one of the pairs of the first memory devices. In some embodiments of the structure, the first memory device includes active devices of a first minimum feature size, and the second memory device includes active devices of a second minimum feature size, the second minimum feature size being larger than the first minimum feature size. In some embodiments of the structure, the first memory device includes first die connectors connected to the front side of the processor device, and the second memory device includes second die connectors connected to the first conductive vias and the back side of the first memory device, the first die connectors having a first pitch, the second die connectors having a second pitch, the second pitch being larger than the first pitch. In some embodiments of the structure, the processor device, the first dielectric layer, and the second dielectric layer are laterally coterminous.

[0130] In an embodiment, a method includes: bonding a first memory device to a wafer, the wafer including a processor device, the first memory device including first conductive vias; forming a first dielectric layer around the first memory device; patterning first openings in the first dielectric layer, the first openings exposing die connectors of the processor device; plating a conductive material in the first openings and on the die connectors; planarizing the conductive material to form second conductive vias in the first openings, the planarizing exposing the first conductive vias of the first memory device; and sawing the first dielectric layer and the wafer to singulate the processor device.

[0131] In some embodiments, the method further includes: before the sawing, bonding a second memory device to the first dielectric layer, the first conductive vias, and the second conductive vias. In some embodiments, the method further includes: before the sawing, forming a redistribution structure on the first dielectric layer, the first conductive vias, and the second conductive vias, the sawing including sawing the redistribution structure.

[0132] The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A structure comprising: a processor device having a first side; a first memory device having a first side and a second side opposite the first side, the first side of the first memory device bonded to the first side of the processor device by metal-to-metal bonds and by dielectric-to-dielectric

bonds; a first dielectric layer laterally surrounding the first memory device; a second memory device having a first side and a second side opposite the first side, the first side of the second memory device bonded to the second side of the first memory device by dielectric-to-dielectric bonds and metal-to-metal bonds, the first memory device being a different type of memory device than the second memory device; a second dielectric layer laterally surrounding the second memory device, a sidewall of the second dielectric layer being laterally coterminous with a sidewall of the first dielectric layer and with a sidewall of the processor device; and a first conductive via extending through the first dielectric layer and the second dielectric layer, the first conductive via connected to the first side of the processor device.

2. The structure of claim 1, wherein the processor device and the first memory device are bonded face-to-face.

3. The structure of claim 1, further comprising: a second conductive via extending through the first dielectric layer, the second conductive via electrically coupling the first side of the processor device to the second memory device.

4. The structure of claim 1, further comprising: a passive device bonded to the first side of the processor device, wherein the first dielectric layer laterally surrounds the passive device.

5. The structure of claim 4, wherein the passive device comprises a through via, further comprising: a second conductive via extending through the second dielectric layer and contacting the through via of the passive device.

6. The structure of claim 1, wherein a width of the first memory device is less than a width of the second memory device.

7. The structure of claim 1, wherein the first memory device is a level 1 cache for the processor device, wherein the second memory device is a level 2 cache for the processor device.

8. A structure comprising: a processor device having a first side, the processor device comprising a semiconductor substrate and an interconnect structure; a first memory device having a first side and a second side opposite the first side, the first side of the first memory device connected to the first side of the processor device by metal-to-metal bonds and by dielectric-to-dielectric bonds; a first dielectric layer laterally surrounding the first memory device; a first conductive via extending through the first dielectric layer, the first conductive via connected to the first side of the processor device; a second memory device having a first side and a second side opposite the first side, the first side of the second memory device connected to the first conductive via and the second side of the first memory device by metal-to-metal bonds, the first side of the second memory device connected to the first dielectric layer and the second side of the first memory device by dielectric-to-dielectric bonds, the first memory device being a different type of memory device than the second memory device; a second dielectric layer laterally surrounding the second memory device; a second conductive via extending through the first dielectric layer and the second dielectric layer to the processor device; and a redistribution structure over the second dielectric layer and the second memory device, wherein the second conductive via electrically couples a conductive feature of the redistribution structure to the processor device.

9. The structure of claim 8, further comprising: an electronic component laterally encapsulated by the first dielectric layer; and a third conductive via extending through the second dielectric layer from the redistribution structure to the electronic component.

10. The structure of claim 9, wherein the electronic component is electrically interposed between the processor device and the redistribution structure.

11. The structure of claim 8, wherein sidewalls of the first dielectric layer are laterally coterminous with sidewalls of the semiconductor substrate and with sidewalls of the interconnect structure.

12. The structure of claim 8, wherein the first memory device is a level 1 cache for the processor device, wherein the second memory device is a level 2 cache for the processor device.

13. The structure of claim 12, wherein the second memory device is a level 3 cache for the processor device.

14. The structure of claim 8, wherein the first memory device has a different minimum feature size than the second memory device.

15. A structure comprising: a processor device having a first side; a first memory device having a first side and a second side opposite the first side, the first side of the first memory device bonded to the first side of the processor device by metal-to-metal bonds and by dielectric-to-dielectric bonds; a second memory device having a first side and a second side opposite the first side, the first side of the second memory device bonded to the first side of the processor device by metal-to-metal bonds and by dielectric-to-dielectric bonds; a first dielectric layer laterally surrounding the first memory device; a combined memory device having a first side and a second side opposite the first side, the first side of the combined memory device bonded to the second side of the first memory device and to the second side of the second memory device by dielectric-to-dielectric bonds and metal-to-metal bonds, the combined memory device having at least two different types of memory; a second dielectric layer laterally surrounding the combined memory device; and a first conductive via extending through the first dielectric layer and the second dielectric layer, the first conductive via connected to the first side of the processor device.

16. The structure of claim 15, wherein the first side of the processor device is a front side of the processor device, wherein the first side of the first memory device is a front side of the first memory device.

17. The structure of claim 16, wherein a first side of the combined memory device is a front side of the combined memory device.

18. The structure of claim 15, further comprising: a second conductive via in the first dielectric layer, wherein the second conductive via electrically connects the combined memory device to the processor device.

19. The structure of claim 15, further comprising: an electronic component bonded to the processor device and laterally encapsulated by the first dielectric layer; and a third conductive via connected to the electronic component and extending through the second dielectric layer.

20. The structure of claim 15, wherein the first memory device is an instruction cache, the second memory device is a data cache, and wherein the combined memory device is a level 2 and a level 3 cache.
