



US012391713B2

(12) **United States Patent**
Kim et al.(10) **Patent No.:** **US 12,391,713 B2**(45) **Date of Patent:** ***Aug. 19, 2025**(54) **ORGANOMETALLIC COMPOUND,
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME, AND ELECTRONIC
APPARATUS INCLUDING THE ORGANIC
LIGHT-EMITTING DEVICE**(71) Applicant: **Samsung Electronics Co., Ltd.**,
Suwon-si (KR)(72) Inventors: **Sangdong Kim**, Seongnam-si (KR);
Seungyeon Kwak, Suwon-si (KR);
Sungjun Kim, Seongnam-si (KR);
Jongsoo Kim, Suwon-si (KR); **Aram**
Jeon, Seoul (KR); **Sunggyu Kang**,
Suwon-si (KR); **Hyun Koo**,
Seongnam-si (KR); **Jiwhan Kim**, Seoul
(KR); **Sukekazu Aratani**, Hwaseong-si
(KR); **Kum Hee Lee**, Suwon-si (KR);
Yongsuk Cho, Hwaseong-si (KR); **Yuri**
Cho, Suwon-si (KR); **Byoungki Choi**,
Hwaseong-si (KR); **Jongwon Choi**,
Yongin-si (KR); **Hyeonho Choi**, Seoul
(KR); **Youngki Hong**, Anyang-si (KR);
Kyuyoung Hwang, Anyang-si (KR)(73) Assignee: **SAMSUNG ELECTRONICS CO.,
LTD.**, Gyeonggi-Do (KR)(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 734 days.This patent is subject to a terminal dis-
claimer.(21) Appl. No.: **16/830,660**(22) Filed: **Mar. 26, 2020**(65) **Prior Publication Data**

US 2020/0308203 A1 Oct. 1, 2020

(30) **Foreign Application Priority Data**Mar. 29, 2019 (KR) 10-2019-0037217
Mar. 25, 2020 (KR) 10-2020-0036054(51) **Int. Cl.****C07F 15/00** (2006.01)
C09K 11/06 (2006.01)
H10K 50/11 (2023.01)
H10K 85/30 (2023.01)
H10K 101/10 (2023.01)(52) **U.S. Cl.**CPC **C07F 15/0033** (2013.01); **C09K 11/06**
(2013.01); **H10K 85/342** (2023.02); **C09K**
2211/185 (2013.01); **H10K 50/11** (2023.02);
H10K 2101/10 (2023.02)(58) **Field of Classification Search**CPC . **C07F 15/0033**; **H01L 51/0085**; **C09K 11/06**;
C09K 2211/185; **H10K 85/342**; **H10K**
50/11; **H10K 2101/10**

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

7,776,458 B2 8/2010 Ragini et al.
8,492,006 B2 7/2013 Ma et al.
9,142,791 B2 9/2015 Adamovich et al.
9,466,804 B2 10/2016 Kishino et al.
9,554,442 B2 1/2017 Kamatani et al.
9,917,264 B2 3/2018 Horiuchi et al.
9,960,370 B2 5/2018 Kishino et al.
10,144,867 B2 12/2018 Ma et al.
10,741,772 B2 8/2020 Lee et al.
11,758,802 B2 * 9/2023 Lee C09K 11/06
428/690

(Continued)

FOREIGN PATENT DOCUMENTS

CN 107722065 A 2/2018
CN 107827933 A 3/2018

(Continued)


OTHER PUBLICATIONS

English Abstract of CN 107722065.

(Continued)

Primary Examiner — Dylan C Kershner(74) *Attorney, Agent, or Firm* — CANTOR COLBURN
LLP(57) **ABSTRACT**Disclosed are an organometallic compound represented by
Formula 1, an organic light-emitting device including the
same, and an electronic device including the organic light-
emitting device:

Formula 1

The detailed description of Formula 1 is the same as
described in the present specification.

(56)

References Cited

U.S. PATENT DOCUMENTS

11,760,769 B2 *	9/2023	Lee	C07F 15/0033	428/690
11,800,788 B2 *	10/2023	Choi	H10K 85/342	
2006/0228582 A1 *	10/2006	Ragini	H05B 33/14	546/10
2010/0219407 A1 *	9/2010	Kamatani	H01L 51/0034	257/E51.026
2010/0270916 A1 *	10/2010	Xia	H10K 85/622	546/10
2012/0217868 A1 *	8/2012	Ma	H10K 85/342	546/4
2013/0334521 A1	12/2013	Lee et al.			
2014/0197389 A1	7/2014	Adamovich et al.			
2015/0001472 A1 *	1/2015	Boudreault	H01L 51/0085	546/4
2015/0021585 A1	1/2015	Yu et al.			
2015/0295188 A1 *	10/2015	Kosuge	H01L 51/0054	345/173
2015/0357587 A1	12/2015	Kishino et al.			
2015/0357588 A1	12/2015	Kwong et al.			
2016/0240800 A1	8/2016	Ma et al.			
2018/0013078 A1	1/2018	Lee et al.			
2018/0198079 A1	7/2018	Boudreault et al.			
2018/0233679 A1	8/2018	Baik et al.			
2019/0013484 A1	1/2019	Kamatani et al.			
2019/0305230 A1	10/2019	Xia et al.			
2020/0099000 A1 *	3/2020	Zhang	C07F 15/0033	
2020/0212319 A1 *	7/2020	Choi	C09B 69/008	
2020/0308201 A1 *	10/2020	Lee	C09K 11/06	
2020/0313095 A1 *	10/2020	Lee	C09K 11/06	
2021/0193938 A1 *	6/2021	Kwak	H10K 85/342	
2021/0355148 A1 *	11/2021	Choi	C07F 15/0033	
2022/0352476 A1 *	11/2022	Boudreault	H10K 85/622	


FOREIGN PATENT DOCUMENTS

JP	2014127688 A	7/2014
JP	2014139147 A	7/2014
KR	20060108127 A1	10/2006
KR	20120026064 A1	3/2012
KR	20140020277 A	2/2014
KR	101468065 B1	12/2014
KR	1020160026744 A	3/2016
KR	1020180005128 A	1/2018
KR	20180082339 A1	7/2018
KR	1020200083198 A	7/2020
KR	1020200115008 A	10/2020
WO	2014007564 A1	1/2014
WO	2014104395 A1	7/2014

OTHER PUBLICATIONS

English Abstract of CN107827933.
 English Abstract of KR 10-1468065.
 Extended European Search Report issued in EP20165793.9, dated May 27, 2020.
 Shiu-Lun Lai, et al., High Efficiency White Organic Light-Emitting Devices Incorporating Yellow Phosphorescent Platinum(II) Complex and Composite Blue Host, Adv. Funct. Mater. 2013, 23, 5168-5176.
 XP055694699 "Transition metal coordination compound used as phosphor material, it's preparation method and application in organic electroluminescence device", 3 pages.
 English Translation of Office Action dated May 18, 2023, issued in corresponding KR Patent Application No. 10-2020-0036054, 7 pp.
 Office Action dated May 18, 2023, issued in corresponding KR Patent Application No. 10-2020-0036054, 8 pp.
 English Translation of Office Action dated Mar. 19, 2024, issued in corresponding KR Application No. 10-2020-0036054, 4 pp.
 Office Action dated Mar. 19, 2024, issued in corresponding KR Application No. 10-2020-0036054, 5 pp.

* cited by examiner



1

**ORGANOMETALLIC COMPOUND,
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME, AND ELECTRONIC
APPARATUS INCLUDING THE ORGANIC
LIGHT-EMITTING DEVICE**

**CROSS-REFERENCE TO RELATED
APPLICATION**

This application claims the priority and benefit of Korean Patent Applications Nos. 10-2019-0037217, filed on Mar. 29, 2019, and 10-2020-0036054, filed on Mar. 25, 2020, in the Korean Intellectual Property Office, the content of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

One or more embodiments relate to an organometallic compound, an organic light-emitting device including the same, and an electronic apparatus including the organic light-emitting device.

2. Description of Related Art

Organic light-emitting devices are self-emission devices, which have improved characteristics in terms of a viewing angle, a response time, brightness, a driving voltage, and a response speed, and produce full-color images.

In an example, an organic light-emitting device includes an anode, a cathode, and an organic layer between the anode and the cathode, wherein the organic layer includes an emission layer. A hole transport region may be between the anode and the emission layer, and an electron transport region may be between the emission layer and the cathode. Holes provided from the anode may move toward the emission layer through the hole transport region, and electrons provided from the cathode may move toward the emission layer through the electron transport region. The holes and the electrons recombine in the emission layer to produce excitons. These excitons transit from an excited state to a ground state, thereby generating light.

SUMMARY

One or more embodiments relate to an organometallic compound, an organic light-emitting device including the same, and an electronic apparatus including the organic light-emitting device.


Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments of the disclosure.

According to one aspect, provided is an organometallic compound represented by Formula 1.

An organometallic compound represented by Formula 1 below.

2

Formula 1



In Formula 1, Y₂ may be C, ring CY₂ may be a C₅-C₃₀ carbocyclic group or a C₁-C₃₀ heterocyclic group,

R₁ to R₈, R₂₀, and A₁ to A₇ may each independently be a group represented by Formula 2-1, a group represented by Formula 2-2, hydrogen, deuterium, —F, —Cl, —Br, —I, —SF₅, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₁-C₆₀ alkylthio group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —B(Q₆)(Q₇), —P(=O)(Q₈)(Q₉), or —P(Q₈)(Q₉),



Z₁ to Z₃ and Z₁₁ to Z₁₃ in Formulae 2-1 and 2-2 may each independently be hydrogen, deuterium, —F, —Cl, —Br, —I, —SF₅, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₁-C₆₀ alkylthio group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted

3

or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), —Ge(Q₃)(Q₄)(Q₅), —B(Q₆)(Q₇), —P(=O)(Q₈)(Q₉) or —P(Q₈)(Q₉), and * indicates a binding site to a neighboring atom,

a2 is an integer of 0 to 20, wherein, when a2 is 2 or more, two or more of R₂₀(s) are identical to or different from each other,

at least one of R₁ to R₈, at least one of R₂₀(s) in the number of a2, or any combination thereof is independently a group represented by Formula 2-1 or a group represented by Formula 2-2,

two or more of R₁ to R₈ are optionally linked together to form a C₅-C₃₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C₁-C₃₀ heterocyclic group unsubstituted or substituted with at least one R_{1a},

two or more R₂₀(s) in the number of a2 are optionally linked together to form a C₅-C₃₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C₁-C₃₀ heterocyclic group unsubstituted or substituted with at least one R_{1a}, two or more of A₁ to A₇ are optionally linked together to form a C₅-C₃₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C₁-C₃₀ heterocyclic group unsubstituted or substituted with at least one R_{1a},

R_{1a} is the same as described in connection with A₇, and a substituent of the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₁-C₆₀ alkylthio group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₂-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is

deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, or a C₁-C₆₀ alkylthio group,

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, or a C₁-C₆₀ alkylthio group, each substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), —Ge(Q₁₃)(Q₁₄)(Q₁₅), —B(Q₁₆)(Q₁₇), —P(=O)(Q₁₈)(Q₁₉), —P(Q₁₈)(Q₁₉), or any combination thereof,

4

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group or a monovalent non-aromatic condensed heteropolycyclic group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₁-C₆₀ alkylthio group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), —Ge(Q₂₃)(Q₂₄)(Q₂₅), —B(Q₂₆)(Q₂₇), —P(=O)(Q₂₈)(Q₂₉), —P(Q₂₈)(Q₂₉), or any combination thereof,

—N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), —Ge(Q₃₃)(Q₃₄)(Q₃₅), —B(Q₃₆)(Q₃₇), —P(=O)(Q₃₈)(Q₃₉), or —P(Q₃₈)(Q₃₉), or

any combination thereof,

wherein Q₁ to Q₉, Q₁₁ to Q₁₉, Q₂₁ to Q₂₉, and Q₃₁ to Q₃₉ may each independently be hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group which is unsubstituted or substituted with deuterium, a C₁-C₆₀ alkyl group, a C₆-C₆₀ aryl group, or any combination thereof, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₁-C₆₀ alkylthio group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group which is unsubstituted or substituted with deuterium, a C₁-C₆₀ alkyl group, a C₆-C₆₀ aryl group, or any combination thereof, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

According to another aspect, provided is an organic light-emitting device including a first electrode, a second electrode, and an organic layer including an emission layer disposed between the first electrode and the second electrode, wherein the organic layer includes at least one organometallic compound represented by Formula 1.

The organometallic compound may be included in the emission layer of the organic layer, and the organometallic compound included in the emission layer may act as a dopant.

According to another aspect, provided is an electronic apparatus including the organic light-emitting device.

BRIEF DESCRIPTION OF THE DRAWING

The above and other aspects, features, and advantages of certain embodiments of the disclosure will be more apparent from the following description taken in conjunction with

5

FIGURE which shows a schematic cross-sectional view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

Reference will now be made in detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the FIGURES, to explain aspects. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

It will be understood that when an element is referred to as being “on” another element, it can be directly on the other element or intervening elements may be present therebetween. In contrast, when an element is referred to as being “directly on” another element, there are no intervening elements present.

It will be understood that, although the terms “first,” “second,” “third” etc. may be used herein to describe various elements, components, regions, layers and/or sections, these elements, components, regions, layers and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer or section from another element, component, region, layer or section. Thus, “a first element,” “component,” “region,” “layer” or “section” discussed below could be termed a second element, component, region, layer or section without departing from the teachings herein.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. As used herein, “a,” “an,” “the,” and “at least one” do not denote a limitation of quantity, and are intended to cover both the singular and plural, unless the context clearly indicates otherwise. For example, “an element” has the same meaning as “at least one element,” unless the context clearly indicates otherwise.

“Or” means “and/or.” As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. It will be further understood that the terms “comprises” and/or “comprising,” or “includes” and/or “including” when used in this specification, specify the presence of stated features, regions, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, regions, integers, steps, operations, elements, components, and/or groups thereof.

Furthermore, relative terms, such as “lower” or “bottom” and “upper” or “top,” may be used herein to describe one element’s relationship to another element as illustrated in the FIGURES. It will be understood that relative terms are intended to encompass different orientations of the device in addition to the orientation depicted in the FIGURES. For example, if the device in one of the FIGURES is turned over, elements described as being on the “lower” side of other elements would then be oriented on “upper” sides of the other elements. The exemplary term “lower,” can therefore, encompass both an orientation of “lower” and “upper,” depending on the particular orientation of the FIGURE. Similarly, if the device in one of the FIGURES is turned

6

over, elements described as “below” or “beneath” other elements would then be oriented “above” the other elements. The exemplary terms “below” or “beneath” can, therefore, encompass both an orientation of above and below.


“About” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, “about” can mean within one or more standard deviations, or within $\pm 30\%$, 20% , 10% or 5% of the stated value.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this disclosure belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the present disclosure, and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

Exemplary embodiments are described herein with reference to cross section illustrations that are schematic illustrations of idealized embodiments. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments described herein should not be construed as limited to the particular shapes of regions as illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as flat may, typically, have rough and/or nonlinear features. Moreover, sharp angles that are illustrated may be rounded. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to illustrate the precise shape of a region and are not intended to limit the scope of the present claims.

An aspect of the present disclosure provides an organometallic compound represented by Formula 1 below:

Formula 1



Y_2 in Formula 1 may be C.

Ring CY_2 in Formula 1 may be a C_5 - C_{30} carbocyclic group or a C_1 - C_{30} heterocyclic group.

For example, ring CY_2 in Formula 1 may be i) a first ring, ii) a second ring, iii) a condensed cyclic group in which two or more first rings are condensed with each other, iv) a condensed cyclic group in which two or more second rings

are condensed with each other, or v) a condensed cyclic group in which at least one first ring is condensed with at least one second ring,

the first ring may be a cyclopentane group, a cyclopentadiene group, a furan group, a thiophene group, a pyrrole group, a silole group, an indene group, a benzofuran group, a benzothiophene group, an indole group, a benzosilole group, an oxazole group, an isoxazole group, an oxadiazole group, an isoxadiazole group, an oxatriazole group, an isoxatriazole group, a thiazole group, an isothiazole group, a thiadiazole group, an isothiadiazo group, a thiatriazole group, an isothiatriazole group, a pyrazole group, an imidazole group, a triazole group, a tetrazole group, an azasilole group, a diazasilole group, or a triazasilole group, and

the second ring may be an adamantane group, a norbornene group, a bicyclo[1.1.1]pentane group, a bicyclo[2.1.1]hexane group, a bicyclo[2.2.1]heptane(norbornane) group, a bicyclo[2.2.2]octane group, a cyclohexane group, a cyclohexene group, a benzene group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, or a triazine group.


In one or more embodiments, ring CY₂ in Formula 1 may be, cyclopentane group, a cyclohexane group, a cyclohexene group, a benzene group, a naphthalene group, an anthracene group, a phenanthrene group, a triphenylene group, a pyrene group, a chrysene group, a 1,2,3,4-tetrahydronaphthalene group, a thiophene group, a furan group, a pyrrole group, a cyclopentadiene group, a silole group, borole group, phosphole group, a selenophene group, a germole group, a benzothiophene group, a benzofuran group, an indole group, an indene group, a benzosilole group, a benzoborole group, a benzophosphole group, a benzoselenophene group, a benzogermole group, a dibenzothiophene group, a dibenzofuran group, a carbazole group, a fluorene group, a dibenzosilole group, a dibenzoborole group, a dibenzophosphole group, a dibenzoselenophene group, a dibenzogermole group, a dibenzothiophene 5-oxide group, 9H-fluorene-9-one group, a dibenzothiophene 5,5-dioxide group, an azabenzothiophene group, an azabenzofuran group, an azaindole group, an azaindene group, an azabenzosilole group, an azabenzoborole group, an azabenzophosphole group, an azabenzoselenophene group, an azabenzogermole group, an azadibenzothiophene group, an azadibenzofuran group, an azacarbazole group, an azafluorene group, an azadibenzosilole group, an azadibenzoborole group, an azadibenzophosphole group, an azadibenzoselenophene group, an azadibenzogermole group, an azadibenzothiophene 5-oxide group, an aza-9H-fluorene-9-one group, an azadibenzothiophene 5,5-dioxide group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a phenanthroline group, a pyrazole group, an imidazole group, a triazole group, an oxazole group, an isoxazole group, a thiazole group, an isothiazole group, an oxadiazole group, a thiadiazole group, a benzopyrazole group, a benzimidazole group, a benzoxazole group, a benzothiazole group, a benzoxadiazole group, a benzothiadiazole group, a 5,6,7,8-tetrahydroisoquinoline group, a 5,6,7,8-tetrahydroquinoline group, an adamantane group, a norbornane group, or a norbornene group.

In one or more embodiments, ring CY₂ in Formula 1 may be a benzene group, a naphthalene group, a 1,2,3,4-tetrahydronaphthalene group, a thiophene group, a furan group, a pyrrole group, a cyclopentadiene group, a silole group, a benzothiophene group, a benzofuran group, an indole group, an indene group, a benzosilole group, a dibenzothiophene


group, a dibenzofuran group, a carbazole group, a fluorene group, or a dibenzosilole group.

In one or more embodiments, ring CY₂ in Formula 1 may be a benzene group, a dibenzothiophene group, a dibenzofuran group, a carbazole group, a fluorene group, or a dibenzosilole group.

R₁ to R₈, R₂₀ and A₁ to A₇ in Formula 1 may each independently be a group represented by Formula 2-1, a group represented by Formula 2-2, hydrogen, deuterium, —F, —Cl, —Br, —I, —SF₅, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₁-C₆₀ alkylthio group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), —Ge(Q₃)(Q₄)(Q₅), —B(Q₆)(Q₇), —P(=O)(Q₈)(Q₉), or —P(Q₈)(Q₉):



Formula 2-1



Formula 2-2

Z₁ to Z₃ and Z₁₁ to Z₁₃ in Formulae 2-1 and 2-2 may each independently be hydrogen, deuterium, —F, —Cl, —Br, —I, —SF₅, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₁-C₆₀ alkylthio group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), —Ge(Q₃)(Q₄)(Q₅), —B(Q₆)(Q₇), —P(=O)(Q₈)(Q₉) or —P(Q₈)(Q₉), and * indicates a binding site to a neighboring atom.

Q₁ to Q₉ are the same as described in the present specification.

Z₁ to Z₃ in Formula 2-1 may be identical to or different from each other.

Z₁₁ to Z₁₃ in Formula 2-2 may be identical to or different from each other.

a2 in Formula 1 indicates the number of $R_{20}(s)$ and may be an integer from 0 to 20. When a2 is 2 or more, two or more of $R_{20}(s)$ may be identical to or different from each other. For example, a2 may be an integer from 0 to 6.

At least one of R_1 to R_8 in Formula 1 (for example, one or two of R_1 to R_8), at least one of $R_{20}(s)$ in the number of a2, or any combination thereof may independently be a group represented by Formula 2-1 or a group represented by Formula 2-2.

In one or more embodiments, R_{20} in Formula 1 may not include a fluoro group ($-F$) and a cyano group. For example, R_{20} may be a group that does not include a fluoro group ($-F$) or a cyano group.

For example, the remaining R_1 to R_8 which are (is) not the group represented by Formula 2-1 or 2-2, the remaining $R_{20}(s)$ which are (is) not the group represented by Formula 2-1 or 2-2, A_1 to A_7 in Formula 1, and Z_1 to Z_3 and Z_{11} to Z_{13} in Formulae 2-1 and 2-2 may each independently be:

hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, $-SF_5$, C_1 - C_{20} alkyl group C_2 - C_{20} alkenyl group, a C_1 - C_{20} alkoxy group, or a C_1 - C_{20} alkylthio group;

a C_1 - C_{20} alkyl group, a C_2 - C_{20} alkenyl group, a C_1 - C_{20} alkoxy group, or C_1 - C_{20} alkylthio group, each substituted with deuterium, $-F$, $-Cl$, $-Br$, $-I$, $-CD_3$, $-CD_2H$, $-CDH_2$, $-CF_3$, $-CF_2H$, $-CFH_2$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group (bicyclo[2.2.1]heptyl group), a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.2]octyl group, a (C_1 - C_{20} alkyl)cyclopentyl group, a (C_1 - C_{20} alkyl)cyclohexyl group, a (C_1 - C_{20} alkyl)cycloheptyl group, a (C_1 - C_{20} alkyl)cyclooctyl group, a (C_1 - C_{20} alkyl)adamantanyl group, a (C_1 - C_{20} alkyl)norbornanyl group, a (C_1 - C_{20} alkyl)norbornenyl group, a (C_1 - C_{20} alkyl)cyclopentenyl group, a (C_1 - C_{20} alkyl)cyclohexenyl group, a (C_1 - C_{20} alkyl)cycloheptenyl group, a (C_1 - C_{20} alkyl)bicyclo[1.1.1]pentyl group, a (C_1 - C_{20} alkyl)bicyclo[2.1.1]hexyl group, a (C_1 - C_{20} alkyl)bicyclo[2.2.2]octyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or any combination thereof;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C_1 - C_{20} alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzo-

quinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranlyl group, a benzothienophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, an azadibenzofuranlyl group or azadibenzothiophenyl group, each unsubstituted or substituted with deuterium, $-F$, $-Cl$, $-Br$, $-I$, $-CD_3$, $-CD_2H$, $-CDH_2$, $-CF_3$, $-CF_2H$, $-CFH_2$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a deuterated C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.2]octyl group, a (C_1 - C_{20} alkyl)cyclopentyl group, a (C_1 - C_{20} alkyl)cyclohexyl group, a (C_1 - C_{20} alkyl)cycloheptyl group, a (C_1 - C_{20} alkyl)cyclooctyl group, a (C_1 - C_{20} alkyl)adamantanyl group, a (C_1 - C_{20} alkyl)norbornanyl group, a (C_1 - C_{20} alkyl)norbornenyl group, a (C_1 - C_{20} alkyl)cyclopentenyl group, a (C_1 - C_{20} alkyl)cyclohexenyl group, a (C_1 - C_{20} alkyl)cycloheptenyl group, a (C_1 - C_{20} alkyl)bicyclo[1.1.1]pentyl group, a (C_1 - C_{20} alkyl)bicyclo[2.1.1]hexyl group, a (C_1 - C_{20} alkyl)bicyclo[2.2.2]octyl group, a phenyl group, a (C_1 - C_{20} alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, an azadibenzofuranlyl group, an azadibenzothiophenyl group, or any combination thereof; or $-N(Q_1)(Q_2)$, $-B(Q_6)(Q_7)$, $-P(=O)(Q_8)(Q_9)$, or $-P(Q_8)(Q_9)$,

wherein Q_1 to Q_9 may each independently be:

deuterium, $-F$, $-CH_3$, $-CD_3$, $-CD_2H$, $-CDH_2$, $-CH_2CH_3$, $-CH_2CD_3$, $-CH_2CD_2H$, $-CH_2CDH_2$, $-CHDCH_3$, $-CHDCH_2H$, $-CHDCHD_2$, $-CHDCH_3$, $-CD_2CD_3$, $-CD_2CD_2H$, $-CD_2CDH_2$, $-CF_3$, $-CF_2H$, $-CFH_2$, $-CH_2CF_3$, $-CH_2CF_2H$, $-CH_2CFH_2$, $-CHFCH_3$, $-CHFCH_2H$, $-CHFCHD_2$, $-CHFCH_3$, $-CF_2CF_3$, $-CF_2CF_2H$, or $-CF_2CFH_2$; or


an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an

11

isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, a phenyl group, a biphenyl group, or a naphthyl group, each unsubstituted or substituted with deuterium, —F, C₁-C₁₀ alkyl group, a phenyl group, or any combination thereof.

In this regard, R₂₀ may not include a fluoro group and a cyano group.


In one or more embodiments, the remaining R₁ to R₈ which are (is) not a group represented by Formulae 2-1 or 2-2, the remaining R₂₀(s) which are (is) not a group represented by Formula 2-1 or 2-2, A₁ to A₇ in Formula 1, and Z₁ to Z₃ and Z to Z₁₃ in Formulae 2-1 and 2-2 may each independently be hydrogen, deuterium, —F, —CH₃, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a C₂-C₁₀ alkenyl group, a C₁-C₁₀ alkoxy group, a C₁-C₁₀ alkylthio group, a group represented by one of Formulae 9-1 to 9-39, a group represented by one of Formulae 9-1 to 9-39 in which at least one hydrogen is substituted with deuterium, a group represented by one of Formulae 9-1 to 9-39 in which at least one hydrogen is substituted with —F, a group represented by one of Formulae 9-201 to 9-237, a group represented by one of Formulae 9-201 to 9-237 in which at least one hydrogen is substituted with deuterium, a group represented by one of Formulae 9-201 to 9-237 in which at least one hydrogen is substituted with —F, a group represented by one of Formulae 10-1 to 10-129, a group represented by one of Formulae 10-1 to 10-129 in which at least one hydrogen is substituted with deuterium, a group represented by one of Formulae 10-1 to 10-129 in which at least one hydrogen is substituted with —F, a group represented by one of Formulae 10-201 to 10-350, a group represented by one of Formulae 10-201 to 10-350 in which at least one hydrogen is substituted with deuterium, or a group represented by one of Formulae 10-201 to 10-350 in which at least one hydrogen is substituted with —F:



9-1
9-2
40
9-3
9-4
45
9-5
9-6
50
9-7
55
9-8
9-9
60
9-10
65

12














-continued



9-11
9-12
9-13
9-14
9-15
9-16
9-17
9-18
9-19
9-20
9-21
9-22
9-23
9-24
9-25
9-26


13

-continued

**14**


-continued

9-27



9-201

9-28 5



9-202

9-29 10




9-203

9-30 15




9-204

9-31 20



9-205

9-32 25



9-206

9-33 30




9-207

9-34 35




9-208

9-35 40




9-209

9-36 45



9-210

9-37 50




9-211

9-38 55

60

9-39











9-212

65

15

-continued

**16**

-continued

9-213


5



9-223

9-214

10



9-224

9-215


15



9-225

9-216


20



9-226

9-217


25



9-227

9-218


30



9-228

9-219


35



9-229

9-220


40



9-230

9-221


45



9-231

9-222


50



9-232

9-223


55



9-233

9-224











60



65

17

-continued

**18**

-continued

9-234

5

9-235

9-236

9-237

10-1

10-2

10-3

10-4

10-5













10-6

10-7

10-8

10-9

65



10-10

10-11

10-12

10-13

10-14

10-15

10-16

10-17

10-18











10-19

10-20

10-21

19


-continued

**20**


-continued

10-22

5




10




10-23

15




10-24

20




10-25

25




10-26

30




10-27

40




10-28

45




10-29

50



10-30


55



60

10-31

65



10-32

10-33

10-34

10-35

10-36

10-37

10-38

10-39










10-40

10-41

10-42

21


-continued

**22**

-continued


10-43

5




10-44 10

15




10-45

20



10-46


25



10-47 30

35


10-48



40


10-49

45




10-50 50

55




10-51

60



65



10-52

10-53

10-54

10-55

10-56

10-57











10-58

10-59

10-60

23

-continued

**24**

-continued

10-61

5

10-62

10

10-63

15

20

10-64

25

10-65

30

10-66

35

10-67

40

10-68

45

50









10-69

55

10-70








60

65



25


-continued

**26**

-continued

10-79


5



10

10-80


15



20

10-81


25



30


10-82

35



10-83


40



45

10-84


50




55

10-85

60



65



10-86

10-87

10-88

10-89

10-90









10-91

10-92

10-93

27


-continued

**28**

-continued

10-94


5




10

10-95

15




20




10-96

25



30


10-97



35


10-98

40



10-99


45



50

10-100


55



60

10-101

65



10-102

10-103

10-104

10-105

10-106

10-107








10-108

10-109

10-110

29


-continued

**30**

-continued

10-111


5



10

10-112


15



20

10-113


25



30

10-114


35



40

10-115

45



10-116


50

55

10-117

60

65



10-118

10-119

10-120







10-121

10-122

10-123

31


-continued



32

10-124

5




10

15

10-125


20



25

10-126

30




35

40

10-127


45



50

10-128

55



60

10-129

65

10-201

10-202













10-203

10-204

10-205

33


-continued

**34**

-continued


10-206

5




10-207

10




10-208

15




10-209

20




10-210

25




10-211

30




10-212

35




10-213

40




10-214

45




10-215

50




10-216

55




10-217

60



10-218

65



10-218

10-219

10-220

10-221

10-222

10-223

10-224

10-225

10-226

10-227










10-228

10-229

10-230

35


-continued

**36**

-continued


10-231

5




10-232

10




10-233

15




10-234

25




10-235

30




10-236

35




10-237

45



10-238

55



10-239

60

65

10-240

10-241

10-242

10-243

10-244









10-245

10-246

10-247

37


-continued

**38**

-continued

10-248


5



10


10-249

15



10-250


20



25


10-251

30



10-252


35



40

10-253


45



50


10-254

55



10-255

60



65

10-256

10-257

10-258

10-259

10-260








10-261

10-262

10-263

39

-continued


**40**

-continued

10-264

5


10



10-265

15


20



10-266

25


30



10-267

35

40



10-268

45

10-269






50

55

10-270

60

65



10-271

10-272

10-273

10-274

10-275

10-276













10-277

10-278

10-279

41


-continued

**42**

-continued

10-280


5



10-292

10-281


10



10-293


10-282

15



10-294


20



10-295

10-283


25



10-296

10-284


30



10-297

10-285


35



10-298

10-286


40



10-299

10-287


45



10-300

10-288


50



10-301

10-289


55



10-302

10-290


60



10-303

10-291









65










10-304

43

-continued








**44**

-continued



45

-continued

**46**

-continued

10-320

5

10

10-321

15

20

10-322

25

30

10-323

35

40

10-324

45

50








10-325

55

10-326

60

65



10-327

10-328

10-329

10-330










10-331

10-332

10-333

47

-continued




48

-continued

10-334


5



10

10-335



15



20


10-336

25




10-337

30




10-338

35




10-339

40



10-340

50



10-341

55

In Formulae 9-1 to 9-39, 9-201 to 9-237, 10-1 to 10-129, and 10-201 to 10-350, * indicates a binding site to a neighboring atom, Ph is a phenyl group, TMS is a trimethylsilyl group, and TMG is a trimethylgermyl.

The “group represented by one of Formulae 9-1 to 9-39 in which at least one hydrogen is substituted with deuterium” and the “group represented by one of Formulae 9-201 to 9-237 in which at least one hydrogen is substituted with deuterium” may be, for example, a group represented by one of Formulae 9-501 to 9-514 and 9-601 to 9-636:

10-342

65



10-343

10-344

10-345

10-346


10-347

10-348

10-349










10-350

9-501



51


-continued

**52**

-continued

9-609

5




9-618

10

9-610


15



9-619

9-611 20


25



9-620

9-612


30



9-621

9-613


35



9-622

9-614 40


45



9-623

9-615


50



9-624

9-616


55



9-625

9-617











65



9-626

53

-continued



The “group represented by one of Formulae 9-1 to 9-39 in which at least one hydrogen is substituted with —F” and the “group represented by one of Formulae 9-201 to 9-237 in

54

which at least one hydrogen is substituted with —F” may be, for example, a group represented by one of Formulae 9-701 to 9-710:

9-627

5



9-701

9-628


10



9-702

9-629


15



9-703

9-630


20



9-704

9-630


20



9-705

9-631


25



9-706

9-632


30



9-707

9-632


35



9-708

9-633


40



9-709

9-634

45



9-710

9-635


50

The “group represented by one of Formulae 10-1 to 10-129 in which at least one hydrogen is substituted with deuterium” and the “group represented by one of Formulae 10-201 to 10-350 in which at least one hydrogen is substituted with deuterium” may be, for example, a group represented by one of Formulae 10-501 to 10-553:


55

9-636

60













10-501



10-502

55


-continued

**56**

-continued


10-503

5



10-513

10-504 10




10-514

15


10-505

20




10-515

10-506 25




10-516

10-507 30



10-517

10-508 35




10-518

40


10-509

45



10-519

10-510 50




10-520

10-511 55










10-512 60

65



57


-continued

**58**

-continued

10-521


5



10


10-522

15




10-523 20

10-524 25




10-525 30

10-526 35




10-527 40

10-528 45




10-529 50

10-530 55



10-531 60

65



10-530

10-531

10-532

10-533








10-534

10-535

10-536

59


-continued

**60**

-continued

10-537


5



10

10-538


15



20

10-540


25



30

10-541


35



40

10-542


45



50


10-543

55



10-544

60



65

10-545

10-546

10-547

10-548

10-549


10-550

10-551








10-552

61

-continued




The “group represented by one of Formulae 10-1 to 10-129 in which at least one hydrogen is substituted with —F” and the “group represented by Formulae 10-201 to 10-350 in which at least one hydrogen is substituted with —F” may be, for example, a group represented by one of Formulae 10-601 to 10-617:

**62**


-continued

10-553

5



10




15

20


10-601

25




10-602

30




10-603

35




10-604

45




10-605

50




10-606

60



10-607

65



10-608

10-609

10-610

10-611

10-612

10-613


10-614

10-615

10-616

63

-continued



In Formula 1, i) two or more of R_1 to R_8 may optionally be linked to form a C_5 - C_{30} carbocyclic group that is unsubstituted or substituted with at least one R_{1a} or a C_1 - C_{30} heterocyclic group that is unsubstituted or substituted with at least one R_{1a} ; ii) two or more $R_{20}(s)$ in the number of a2 may optionally be linked to form a C_5 - C_{30} carbocyclic group that is unsubstituted or substituted with at least one R_{1a} or a C_1 - C_{30} heterocyclic group that is unsubstituted or substituted with at least one R_{1a} ; and iii) two or more of A_1 to A_7 may optionally be linked to form a C_5 - C_{30} carbocyclic group that is unsubstituted or substituted with at least one R_{1a} or a C_1 - C_{30} heterocyclic group that is unsubstituted or substituted with at least one R_{1a} .

R_{1a} is the same as described in connection with A_7 .

In one or more embodiments, R_1 to R_8 , R_{20} and A_7 in Formula 1 may each independently be a group represented by Formula 2-1, a group represented by Formula 2-2, hydrogen, deuterium, $-F$, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted phenyl group, or a substituted or unsubstituted biphenyl group.

In one or more embodiments, Z_1 to Z_3 and Z_{11} to Z_{13} in Formulae 2-1 and 2-2 may each independently be hydrogen, deuterium, $-F$, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted phenyl group, or a substituted or unsubstituted biphenyl group.

In one or more embodiments, R_1 to R_8 and A_7 in Formula 1 may each independently be:

a group represented by Formula 2-1 or a group represented by Formula 2-2;

hydrogen, deuterium, or $-F$; or

a C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a phenyl group, or a biphenyl group, each unsubstituted or substituted with deuterium, $-F$, C_1 - C_{20} alkyl group, a deuterated C_1 - C_{20} alkyl group, a fluorinated C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, a deuterated C_3 - C_{10} cycloalkyl group, a fluorinated C_3 - C_{10} cycloalkyl group, a $(C_1$ - C_{20} alkyl) C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a deuterated C_1 - C_{10} heterocycloalkyl group, a fluorinated C_1 - C_{10} heterocycloalkyl group, a $(C_1$ - C_{20} alkyl) C_1 - C_{10} heterocycloalkyl group, a phenyl group, a deuterated phenyl group, a fluorinated phenyl group, a $(C_1$ - C_{20} alkyl)phenyl group, a biphenyl group, a deuterated biphenyl group, a fluorinated biphenyl group, a $(C_1$ - C_{20} alkyl)biphenyl group, or any combination thereof.

In one or more embodiments, R_{20} in Formula 1 may be: a group represented by Formula 2-1 or a group represented by Formula 2-2;

hydrogen or deuterium; or

a C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a phenyl group, or a biphenyl group, each unsubstituted or substituted with deuterium, a C_1 - C_{20} alkyl group, a deuterated C_1 - C_{20} alkyl group, a C_3 - C_{10}

64

cycloalkyl group, a deuterated C_3 - C_{10} cycloalkyl group, a $(C_1$ - C_{20} alkyl) C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a deuterated C_1 - C_{10} heterocycloalkyl group, a $(C_1$ - C_{20} alkyl) C_1 - C_{10} heterocycloalkyl group, a phenyl group, a deuterated phenyl group, a $(C_1$ - C_{20} alkyl)phenyl group, a biphenyl group, a deuterated biphenyl group, a $(C_1$ - C_{20} alkyl)biphenyl group, or any combination thereof.

In one or more embodiments, at least one of R_1 to R_8 in Formula 1 may independently be a group represented by Formula 2-1 or a group represented by Formula 2-2.

In one or more embodiments, at least one of R_3 and R_5 in Formula 1 may independently be a group represented by Formula 2-1 or a group represented by Formula 2-2.

In one or more embodiments, at least one of remaining R_1 to R_8 which are (is) not the group represented by Formula 2-1 or 2-2, at least one of remaining $R_{20}(s)$ which are (is) not the group represented by Formulae 2-1 or 2-2, or any combination thereof may each independently be i) an electron withdrawing group, ii) an electron donating group, iii) a soluble group, or iv) a polymer, oligomer or dendrimer forming moiety-containing group. When at least one of the remaining R_1 to R_8 which are (is) not the group represented by Formula 2-1 or 2-2, at least one of the remaining $R_{20}(s)$ which are (is) not the group represented by Formulae 2-1 or 2-2, or any combination thereof are each independently i) an electron-withdrawing group, ii) electron-donating group, iii) a soluble group, or iv) a polymer, oligomer or dendrimer forming moiety-containing group, then the organometallic compound represented by Formula 1 may have excellent electron transport capability and hole transport capability, and solubility with respect to water and/or an organic solvent, or may form a polymer, an oligomer, or a dendrimer by an additional reaction. Accordingly, the organometallic compound represented by Formula 1 can be used as a material for use in an electronic device, for example, a material for use in an organic layer of organic light-emitting device.

The electron-withdrawing group is a group that can withdraw electrons, and an example thereof is:

$-F$, $-Cl$, $-Br$, $-I$, a cyano group, or a nitro group; or

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_1 - C_{60} alkylthio group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group or monovalent non-aromatic condensed heteropolycyclic group, each substituted $-F$, $-Cl$, $-Br$, $-I$, a cyano group, a nitro group, or any combination thereof.

For example, the electron-withdrawing group may be a fluoro group or a fluorinated C_1 - C_{60} alkyl group.

In one or more embodiments, the electron-withdrawing group may be:

$-F$; or

a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a

tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, or a tert-decyl group, each substituted with at least one —F.

The electron-donating group is a group that is able to donate electrons, and may be, for example, a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a cyclooctenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a carbazolyl group, a fluorenyl group, a dibenzosilolyl group, a dibenzofuranyl group, or a dibenzothiophenyl group, each unsubstituted or substituted with deuterium, a C₁-C₂₀ alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a cyclooctenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a carbazolyl group, a fluorenyl group, a dibenzosilolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, or any combination thereof.

The soluble group may be a group that improves the solubility of the organometallic compound represented by Formula 1 with respect to water and/or various organic solvents, and may be, for example:

a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a C₁-C₆₀ alkylthio group, C₁-C₆₀ carboxy group, C₁-C₆₀ oxycarbonyl group, a C₁-C₆₀ amide group, a C₁-C₆₀ carbamate group, or a C₁-C₆₀ urea group; or

a fluorenyl group, each unsubstituted or substituted with a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a C₁-C₆₀ alkylthio group, a C₁-C₆₀ carboxy group, a C₁-C₆₀ oxycarbonyl group, a C₁-C₆₀ amide group, a C₁-C₆₀ carbamate, a C₁-C₆₀ urea group, or any combination thereof.

The polymer, oligomer or dendrimer forming moiety-containing group may be a group that includes at least one moiety that can form a polymer, an oligomer, or a dendrimer by an additional reaction, and the polymer, oligomer or dendrimer forming moiety may be a vinyl group or a cyclopropanyl group.

For example, the polymer, oligomer or dendrimer forming moiety-containing group may be a phenyl group substituted with at least one vinyl group.

In one or more embodiments, at least one of R₃, R₄, R₆, R₇, and A₇ (for example, one, two, or three of R₃, R₄, R₆, R₇, and A₇) may independently be an electron-withdrawing group.

In one or more embodiments, at least one of R₄, R₆ and A₇ may independently be an electron-withdrawing group.

In one or more embodiments, at least one of R₂₀(s) in the number of a2 may independently be an electron-donating group or a soluble group.

In one or more embodiments, at least one of remaining R₁ to R₈ which are (is) not the group represented by Formula 2-1 or 2-2 may each independently be:

—F; or

a fluorinated C₁-C₂₀ alkyl group, a fluorinated C₃-C₁₀ cycloalkyl group, a fluorinated C₁-C₁₀ heterocycloalkyl group, a fluorinated phenyl group, or a fluorinated a biphenyl group, each unsubstituted or substituted with deuterium, —F, C₁-C₂₀ alkyl group, a deuterated C₁-C₂₀ alkyl group, a fluorinated C₁-C₂₀ alkyl group, a C₃-C₁₀ cycloalkyl group, a deuterated C₃-C₁₀ cycloalkyl group, a fluorinated C₃-C₁₀ cycloalkyl group, a (C₁-C₂₀ alkyl)C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a deuterated C₁-C₁₀ heterocycloalkyl group, a fluorinated C₁-C₁₀ heterocycloalkyl group, a (C₁-C₂₀ alkyl)C₁-C₁₀ heterocycloalkyl group, a phenyl group, a deuterated a phenyl group, a fluorinated a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a deuterated a biphenyl group, a fluorinated a biphenyl group, a (C₁-C₂₀ alkyl)biphenyl group, or any combination thereof.

In one or more embodiments, at least one of remaining R₁ to R₈ which are (is) not the group represented by Formula 2-1 or 2-2 among R₁ to R₈ in Formula 1 may each independently be:

deuterium; or

a deuterated C₁-C₂₀ alkyl group, a deuterated C₃-C₁₀ cycloalkyl group, a deuterated C₁-C₁₀ heterocycloalkyl group, a deuterated a phenyl group, or a deuterated a biphenyl group, each unsubstituted or substituted with deuterium, a C₁-C₂₀ alkyl group, a deuterated C₁-C₂₀ alkyl group, a C₃-C₁₀ cycloalkyl group, a deuterated C₃-C₁₀ cycloalkyl group, a (C₁-C₂₀ alkyl)C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a deuterated C₁-C₁₀ heterocycloalkyl group, a (C₁-C₂₀ alkyl)C₁-C₁₀ heterocycloalkyl group, a phenyl group, a deuterated a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a deuterated a biphenyl group, a (C₁-C₂₀ alkyl)biphenyl group, or any combination thereof.

In one or more embodiments, at least one of remaining R₁ to R₈ which are (is) not the group represented by Formula 2-1 or 2-2 may each independently be:

hydrogen; or

a C₁-C₂₀ alkyl group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a phenyl group, or a biphenyl group, each unsubstituted or substituted with a C₁-C₂₀ alkyl group, a C₃-C₁₀ cycloalkyl group, a (C₁-C₂₀ alkyl)C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a (C₁-C₂₀ alkyl)C₁-C₁₀ heterocycloalkyl group, a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a (C₁-C₂₀ alkyl)biphenyl group, or any combination thereof.

In one or more embodiments, at least one of A₁ to A₆ in Formula 1 may not be hydrogen.

In one or more embodiments, A₇ in Formula 1 may not be hydrogen.

In one or more embodiments, A₇ in Formula 1 may be an electron-withdrawing group.

In one or more embodiments, a group represented by *—C(A₁)(A₂)(A₃) and a group represented by *—C(A₄)(A₅)(A₆) in Formula 1 may be identical to each other.

In one or more embodiments, a group represented by *—C(A₁)(A₂)(A₃) and a group represented by *—C(A₄)(A₅)(A₆) in Formula 1 may be different from each other.

In one or more embodiments, the organometallic compound represented by Formula 1 may satisfy at least one of Condition 1 to Condition 3:

Condition 1

A₁ to A₆ in Formula 1 may each independently be a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₂-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

Condition 2

at least one of A₁ to A₆ in Formula 1 may be a substituted or unsubstituted C₂-C₆₀ alkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₂-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and

Condition 3

A₇ in Formula 1 may be deuterium, —F, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₂-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

In one or more embodiments, the organometallic compound represented by Formula 1 may satisfy Condition 1. When Condition 1 is satisfied, two advantages can be obtained:

(1) Although not intended to be limited by a specific theory, since an α-proton has about 105 times greater chemical reactivity than a β-proton, the α-proton may form various forms of intermediates during synthesis of compounds and/or storage, causing side reactions. However, since A₁ to A₆ in Formula 1 are defined as in Condition 1, the carbons linked to A₁ to A₆ in Formula 1 may not include α-protons. Accordingly, the organometallic compound represented by Formula 1 may have a stable chemical structure that minimizes the occurrence of side reactions before and after synthesis, and at the same time, may minimize the interaction between the organometallic compound molecules during operation of the electronic device (for example, an organic light emitting device) including the same.

(2) Furthermore, since Formula 1 contains an ancillary ligand (O'O ligand in Formula 1) that is structurally bulky and has a strong electron-donating capability, the interaction between the ancillary ligand and a main ligand (N'C in Formula 1) may be enhanced, and thus, the rigidity of the organometallic compound represented by Formula 1 may be improved. Thus, the full width at half maximum (FWHM) of the emission peak in the photoluminescence (PL) spectrum or electroluminescence (EL) spectrum of the organometallic compound represented by Formula 1 may be decreased, and the vibronic state of the molecule of the organometallic compound represented by Formula 1 may be reduced and thus, emission transition and photoalignment ability can be improved.

In one or more embodiments, the organometallic compound represented by Formula 1 may satisfy at least one of Condition 4 and Condition 5

Condition 4

two or more of A₁ to A₃ in Formula 1 may be linked together, and thus a group represented by *—C(A₁)(A₂)(A₃) becomes (or, is) a C₅-C₃₀ carbocyclic group that is unsubstituted or substituted with at least one R_{1a} or a C₁-C₃₀ heterocyclic group that is unsubstituted or substituted with at least one R_{1a};

Condition 5


two or more of A₄ to A₆ in Formula 1 may be linked together, and thus a group represented by *—C(A₄)(A₅)(A₆) becomes (or, is) a C₅-C₃₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C₁-C₃₀ heterocyclic group unsubstituted or substituted with at least one R_{1a}.

In one or more embodiments, the organometallic compound represented by Formula 1 may include at least one deuterium.


In one or more embodiments, at least one of R₁ to R₈ in Formula 1 may include at least one deuterium.

In one or more embodiments, at least one of R₂₀(s) in the number of a2 of Formula 1 may include deuterium.


In one or more embodiments, a group represented by



in Formula 1 may be a group represented by one of Formulae CY1 to CY108:









CY1



CY2

69


-continued

**70**

-continued


CY3

5




10

CY4 15




20

CY5 25




30

CY6 35




40

CY7 45




50

CY8 55



60

65



CY9

CY10

CY11

CY12








CY13

CY14

CY15

71


-continued

**72**

-continued

CY16


5



CY23

CY17

10




CY24

15

CY18

20




CY25

25

CY19

30




CY26

35

CY20

40




CY27

45

CY21

50




CY28

55

CY22

60









CY29

65

73

-continued


**74**

-continued

CY30

5

10




CY36

CY31

15

20

25




CY37

CY32

30

35




CY38

CY33

40

45




CY39

CY34

50

55




CY40

CY35

60







65



CY41

75


-continued

**76**

-continued


CY42

5




10

CY43 15



20


CY44 25



30

35


CY45



40

45


CY46



50

55

CY47



60

65

CY48

CY49

CY50

CY51







CY52

CY53

CY54

77


-continued

**78**

-continued

CY55


5



10

CY56


15



20

CY57


25



30

CY58


35



40

CY59

45




50

55

CY60

60



65

CY61

CY62

CY63







CY64

CY65

CY66

79


-continued

**80**

-continued

CY67

5




CY73

10

CY68

15




CY74

20

CY69

25




CY75

30

CY70

35




CY76

40

CY71

45




CY77

50

55

CY72

60









CY78

65

81


-continued

**82**

-continued

CY79


5



CY85

CY80

15




CY86

20

25

CY81

30




CY87

35

CY82

40




CY88

45

CY83

50




CY89

55

CY84

60








CY90

65

83


-continued

**84**

-continued

CY91


5



10

CY92


20



25

CY93

30




35

40

CY94


45



50

CY95

60



65

CY96

CY97






CY98

CY99

CY100

85


-continued

**86**

-continued

CY101

5




10

CY102

15

20

25




CY103

30

35

40



CY106

CY107

CY108

CY104

45

In Formulae CY1 to CY108,
T₂ to T₈ may each independently be a group represented
by Formula 2-1 or a group represented by Formula 2-2,

R₂ to R₈ and R_{1a} are the same as described in the present
specification, and R₂ to R₈ are not hydrogen,

* is a binding site to Ir in Formula 1, and

*'' is a binding site to a neighboring atom in Formula 1.


For example, a group represented by

CY105

55

60


65








in Formula 1 may be a group represented by Formula CY9,
CY11, CY12, CY14, or CY76.

87






In one or more embodiments, a group represented by



in Formula 1 may be a group represented by one of Formulae A(1) to A(10):

**88**

-continued



In Formulae A(1) to A(10),

Y_2 is C,

X_{21} is O, S, N(R_{25}), C(R_{25})(R_{26}), or Si(R_{25})(R_{26}),

R_9 to R_{12} and R_{21} to R_{26} are the same as described in connection with R_{20} ,

*' is a binding site to Ir in Formula 1, and

*'' is a binding site to a neighboring atom in Formula 1.

In one or more embodiments, R_9 and R_{11} in Formula A(1) may not be hydrogen.

89

In one or more embodiments, R_{10} and R_{12} in Formula A(1) may each independently be hydrogen or deuterium.

In one or more embodiments, R_9 and R_{11} in Formula A(1) may not be hydrogen, and R_{10} and R_{12} may each be hydrogen.

In one or more embodiments, R_9 and R_{11} in Formula A(1) may be identical to each other.

In one or more embodiments, R_9 and R_{11} in Formula A(1) may be different from each other.

In one or more embodiments, R_9 and R_{11} in Formula A(1) may be different from each other, and the number of carbons included in R_9 may be different from the number of carbons included in R_{11} .

In one or more embodiments, R_9 and R_{11} in Formula A(1) may be different from each other, and the number of carbons included in R_{11} may be greater than the number of carbons included in R_9 .

In one or more embodiments, R_9 and R_{11} in Formula A(1) may each independently be:

deuterium; or

a C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a phenyl group, or a biphenyl group, each unsubstituted or substituted with deuterium, a C_1 - C_{20} alkyl group, a deuterated C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, a deuterated C_3 - C_{10} cycloalkyl group, a $(C_1$ - C_{20} alkyl) C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a deuterated C_1 - C_{10} heterocycloalkyl group, a $(C_1$ - C_{20} alkyl) C_1 - C_{10} heterocycloalkyl group, a phenyl group, a deuterated phenyl group, a $(C_1$ - C_{20} alkyl)phenyl group, a biphenyl group, a deuterated biphenyl group, a $(C_1$ - C_{20} alkyl)biphenyl group, or any combination thereof.





In one or more embodiments, i) at least one of R_9 to R_{12} in Formula A(1), ii) R_9 , R_{10} , one of R_{21} to R_{26} , or any combination thereof in Formulae A(2), A(9), and A(10), iii) R_9 , R_{12} , one of R_{21} to R_{26} , or any combination thereof in Formulae A(3), A(6), and A(8), and iv) R_{11} , R_{12} , one of R_{21} to R_{26} , or any combination thereof in Formulae A(4), A(5), and A(7) may each independently be deuterated C_1 - C_{20} alkyl group, a deuterated C_3 - C_{10} cycloalkyl group, a deuterated C_1 - C_{10} heterocycloalkyl group, a deuterated phenyl group, or deuterated biphenyl group, each unsubstituted or substituted with deuterium, a C_1 - C_{20} alkyl group, a deuterated C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, a deuterated C_3 - C_{10} cycloalkyl group, a $(C_1$ - C_{20} alkyl) C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a deuterated C_1 - C_{10} heterocycloalkyl group, a $(C_1$ - C_{20} alkyl) C_1 - C_{10} heterocycloalkyl group, a phenyl group, a deuterated phenyl group, a $(C_1$ - C_{20} alkyl)phenyl group, a biphenyl group, a deuterated biphenyl group, a $(C_1$ - C_{20} alkyl)biphenyl group, or any combination thereof.

In one or more embodiments, at least one of R_9 and R_{11} in Formula A(1) (for example, R_9 and R_{11} in Formula A(1)) may independently be deuterated C_1 - C_{20} alkyl group, a deuterated C_3 - C_{10} cycloalkyl group, a deuterated C_1 - C_{10} heterocycloalkyl group, a deuterated phenyl group, or a deuterated biphenyl group, each optionally substituted with a C_1 - C_{20} alkyl group, a deuterated C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, a deuterated C_3 - C_{10} cycloalkyl group, a $(C_1$ - C_{20} alkyl) C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a deuterated C_1 - C_{10} heterocycloalkyl group, a $(C_1$ - C_{20} alkyl) C_1 - C_{10} heterocycloalkyl group, a phenyl group, a deuterated phenyl group, a $(C_1$ - C_{20} alkyl)phenyl group, a biphenyl group, a deuterated biphenyl group, a $(C_1$ - C_{20} alkyl)biphenyl group, or any combination thereof.

In the present specification, TMS represents * —Si(CH_3)₃, and TMG represents * —Ge(CH_3)₃.


90

The organometallic compound represented by Formula 1 may be one of Compounds 1 to 16:



91

-continued



5


5

10

15

20

6




25

30

35

7




40

45

50

8




55

60

65


92

-continued




9

10




11



93

-continued




12

5

10

15

13




20

25

30

14




35

40

45

15



50

55


60

65

94

-continued

16



At least one of R_1 to R_8 in Formula 1, at least one of $R_{20}(s)$ in the number of a2, or any combination thereof may independently be a group represented by Formula 2-1 or a group represented by Formula 2-2.

As such, electronic devices, such as organic light-emitting devices, including organometallic compounds represented by Formula 1 may have high luminescence efficiency. Although not limited to a particular theory, at least one of R_1 to R_8 in Formula 1, at least one of $R_{20}(s)$ in the number of a2 of Formula 1, or any combination thereof may be a group represented by Formula 2-1 or a group represented by Formula 2-2. Accordingly, since the oscillation strength of the S_n excitation level ($n > 3$) of the organometallic compound represented by Formula 1 is, for example, 0.1 or more (and/or), the oscillation strength of S_n is greater than the oscillation strength corresponding to S_1 , S_2 , and S_3 (and/or), and the S_n - T_1 energy gap is less than 1 eV, the organic light-emitting device using the organometallic compounds represented by Formula 1 may have high luminescence efficiency.

Accordingly, an electronic device using the organometallic compound represented by Formula 1, for example, an organic light-emitting device using the organometallic compound represented by Formula 1 may have high luminescence efficiency and/or long lifespan.

The highest occupied molecular orbital (HOMO) energy level, lowest unoccupied molecular orbital (LUMO) energy level, energy gap, T_1 energy level, S_1 energy level, gap between S_5 and T_1 , and S_5 oscillation strength of the organometallic compound represented by Formula 1 were evaluated using the Gaussian 09 program with the molecular structure optimization obtained by B3LYP-based density functional theory (DFT), and results thereof are shown in Table 1.

TABLE 1

Compound No.	HOMO (eV)	LUMO (eV)	Energy gap (eV)	T ₁ (eV)	S ₁ (eV)	S _S - T ₁ Gap (eV)	S _S Oscillation Strength
1	-4.61	-1.70	2.91	2.05	2.29	0.80	0.2424
2	-4.57	-1.69	2.88	2.02	2.26	0.71	0.1742
3	-4.69	-1.82	2.87	2.02	2.25	0.80	0.2437
4	-4.77	-1.93	2.84	2.01	2.23	0.79	0.2426
5	-4.74	-1.90	2.84	2.00	2.23	0.80	0.2476
6	-4.76	-1.94	2.82	1.99	2.21	0.80	0.2464
7	-4.67	-1.75	2.92	2.06	2.31	0.75	0.1123
8	-4.63	-1.77	2.87	2.01	2.26	0.84	0.1848
9	-4.70	-1.85	2.84	1.97	2.25	0.82	0.1434
10	-4.68	-1.87	2.81	2.00	2.23	0.82	0.1257

15

From Table 1, it is confirmed that the organometallic compound represented by Formula 1 has such electric characteristics that are suitable for use as a dopant for an electric device, for example, an organic light-emitting device.

In one or more embodiments, the full width at half maximum (FWHM) of the emission peak of the emission spectrum or the electroluminescence spectrum of the organometallic compound may be 55 nm or less. For example, the FWHM of the emission peak of the emission spectrum or the electroluminescence spectrum of the organometallic compound may be from about 30 nm to about 55 nm, about 40 nm to about 53 nm, or about 45 nm to about 52 nm.

In one or more embodiments, the maximum emission wavelength (emission peak wavelength, λ_{max}) of the emission peak of the emission spectrum or the electroluminescence spectrum of the organometallic compound may be from about 610 nm to about 640 nm.

In one or more embodiments, the HOMO energy level of the organometallic compound represented by Formula 1 may be from about -5.200 eV to about -5.000 eV. The HOMO energy level may be measured by using cyclic voltammetry. For example, the HOMO energy level may be measured using the method described in Table 2 below.

In one or more embodiments, the LUMO energy level of the organometallic compound represented by Formula 1 may be from about -2.700 eV to about -2.300 eV. The LUMO energy level may be measured by using cyclic voltammetry. For example, the HOMO energy level may be measured using the method described in Table 2 below.

In one or more embodiments, the decay time of the organometallic compound represented by Formula 1 may be 0.8 μ s or less, for example, from about 0.6 μ s to about 0.8 μ s. The decay time may be estimated from the time-resolved photoluminescence (TRPL) spectrum of the organometallic compound. For example, the decay time evaluation method of the organometallic compound may refer to the method described in Evaluation Example 2 herein.

In one or more embodiments, the horizontal orientation ratio of the transition dipole moment of the organometallic compound represented by Formula 1 may be from about 90% to about 100%.

For example, the horizontal orientation ratio of the transition dipole moment of the organometallic compound may be, for example, from about 90% to about 100%, from about 91% to 100%, from about 92% to about 100%, from about 93% to about 100%, from about 94% to about 100%, from about 95% to about 100%, from about 96% to about 100%, from about 97% to about 100%, from about 98% to about 100%, or from about 99% to about 100%, or 100%.

The horizontal orientation ratio of the transition dipole moment may be evaluated using an angle-dependent PL measurement apparatus. For a description of the angle-dependent PL measurement apparatus may refer to, for example, the angle-dependent PL measurement apparatus described in KR Application No. 2013-0150834, herein incorporated by reference.

As described above, since the horizontal orientation ratio of the transition dipole moment of the organometallic compound is high, when an organic light-emitting device including the organometallic compound is driven, an electric field is emitted in a direction that is substantially parallel with respect to the film containing the organometallic compound, and thus, the light loss due to the waveguide mode and/or surface plasmon polariton mode can be reduced. The light emitted according to this mechanism may have high external extraction efficiency (that is, the external extraction efficiency of light emitted from the organometallic compound from a device (for example, an organic light-emitting device) including a film (for example, an emission layer to be described later) containing the organometallic compound). Accordingly, an electronic device including the organometallic compound, for example, an organic light-emitting device including the organometallic compound may have high luminescence efficiency.

Synthesis methods of the organometallic compound represented by Formula 1 may be recognizable by one of ordinary skill in the art by referring to Synthesis Examples provided below.

The organometallic compound represented by Formula 1 is suitable for use in an organic layer of an organic light-emitting device, for example, for use as a dopant in an emission layer of the organic layer. Thus, another aspect provides an organic light-emitting device that includes: a first electrode; a second electrode; and an organic layer that is disposed between the first electrode and the second electrode and includes an emission layer, wherein the organic layer includes at least one organometallic compound represented by Formula 1.

Since the organic light-emitting device has an organic layer containing the organometallic compound represented by Formula 1 as described above, excellent characteristics may be obtained with respect to driving voltage, current efficiency, external quantum efficiency, a roll-off ratio, and lifespan, and the FWHM of the emission peak of the EL spectrum is relatively narrow.

The organometallic compound of Formula 1 may be used between a pair of electrodes of an organic light-emitting device. For example, the organometallic compound represented by Formula 1 may be included in the emission layer. In this regard, the organometallic compound may act as a

dopant, and the emission layer may further include a host (that is, an amount of the organometallic compound represented by Formula 1 in the emission layer is smaller than an amount of the host).

In one or more embodiments, the emission layer may emit red light.

The expression “(an organic layer) includes at least one of organometallic compounds” used herein may include a case in which “(an organic layer) includes identical organometallic compounds represented by Formula 1” and a case in which “(an organic layer) includes two or more different organometallic compounds represented by Formula 1”.

For example, the organic layer may include, as the organometallic compound, only Compound 1. In this regard, Compound 1 may exist only in the emission layer of the organic light-emitting device. In one or more embodiments, the organic layer may include, as the organometallic compound, Compound 1 and Compound 2. In this regard, Compound 1 and Compound 2 may exist in an identical layer (for example, Compound 1 and Compound 2 all may exist in an emission layer).

The first electrode may be an anode, which is a hole injection electrode, and the second electrode may be a cathode, which is an electron injection electrode; or the first electrode may be a cathode, which is an electron injection electrode, and the second electrode may be an anode, which is a hole injection electrode.

In one or more embodiments, in the organic light-emitting device, the first electrode is an anode, and the second electrode is a cathode, and the organic layer may further include a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode, and the hole transport region may include a hole injection layer, a hole transport layer, an electron blocking layer, a buffer layer, or any combination thereof, and the electron transport region may include a hole blocking layer, an electron transport layer, an electron injection layer, or any combination thereof.

The term “organic layer” used herein refers to a single layer and/or a plurality of layers between the first electrode and the second electrode of the organic light-emitting device. The “organic layer” may include, in addition to an organic compound, an organometallic complex including metal.

FIGURE is a schematic cross-sectional view of an organic light-emitting device 10 according to an embodiment. Hereinafter, the structure of an organic light-emitting device according to an embodiment and a method of manufacturing an organic light-emitting device according to an embodiment will be described in connection with FIGURE. The organic light-emitting device 10 includes a first electrode 11, an organic layer 15, and a second electrode 19, which are sequentially stacked.

A substrate may be additionally located under the first electrode 11 or above the second electrode 19. For use as the substrate, any substrate that is used in organic light-emitting devices available in the art may be used, and the substrate may be a glass substrate or a transparent plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

In one or more embodiments, the first electrode 11 may be formed by depositing or sputtering a material for forming the first electrode 11 on the substrate. The first electrode 11 may be an anode. The material for forming the first electrode 11 may include materials with a high work function to

facilitate hole injection. The first electrode 11 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. The material for forming the first electrode 11 may be indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), or zinc oxide (ZnO). In one or more embodiments, the material for forming the first electrode 11 may be metal, such as magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag).

The first electrode 11 may have a single-layered structure or a multi-layered structure including two or more layers. For example, the first electrode 11 may have a three-layered structure of ITO/Ag/ITO.

The organic layer 15 is located on the first electrode 11. The organic layer 15 may include a hole transport region, an emission layer, and an electron transport region.

The hole transport region may be between the first electrode 11 and the emission layer.

The hole transport region may include a hole injection layer, a hole transport layer, an electron blocking layer, a buffer layer, or any combination thereof.

The hole transport region may include only either a hole injection layer or a hole transport layer. In one or more embodiments, the hole transport region may have a hole injection layer/hole transport layer structure or a hole injection layer/hole transport layer/electron blocking layer structure, wherein, for each structure, each layer is sequentially stacked in this stated order from the first electrode 11.

When the hole transport region includes a hole injection layer (HIL), the hole injection layer may be formed on the first electrode 11 by using one or more suitable methods, for example, vacuum deposition, spin coating, casting, and/or Langmuir-Blodgett (LB) deposition.


When a hole injection layer is formed by vacuum deposition, the deposition conditions may vary according to a material that is used to form the hole injection layer, and the structure and thermal characteristics of the hole injection layer. For example, the deposition conditions may include a deposition temperature of about 100° C. to about 500° C., a vacuum pressure of about 10⁻⁸ torr to about 10⁻³ torr, and a deposition rate of about 0.01 Å/sec to about 100 Å/sec. However, the deposition conditions are not limited thereto.

When the hole injection layer is formed using spin coating, coating conditions may vary according to the material used to form the hole injection layer, and the structure and thermal properties of the hole injection layer. For example, a coating speed may be from about 2,000 rpm to about 5,000 rpm, and a temperature at which a heat treatment is performed to remove a solvent after coating may be from about 80° C. to about 200° C. However, the coating conditions are not limited thereto.

Conditions for forming a hole transport layer and an electron blocking layer may be understood by referring to conditions for forming the hole injection layer.


The hole transport region may be m-MTDATA, TDATA, 2-TNATA, NPB, β-NPB, TPD, Spiro-TPD, Spiro-NPB, methylated-NPB, TAPC, HMTPD, 4,4',4"-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrenesulfonate) (PANI/PSS), TFB(Poly[(9,9-dioctylfluorenyl-2,7-diyl)-co-(4,4'-(N-(4-sec-butylphenyl)diphenylamine))]), a compound represented by Formula 201 below, a compound represented by Formula 202 below, or any combination thereof:

99




100

-continued




101


-continued



methylated NPB




TAPC



HMTDP


Formula 201



102

-continued

Formula 202



Ar₁₀₁ and Ar₁₀₂ in Formula 201 may each independently be a phenylene group, a pentalenylene group, an indenylene group, a naphthalenylene group, an azulenylene group, a heptalenylene group, an acenaphthylenylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, or a pentacenylene group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, or any combination thereof.

The designations xa and xb in Formula 201 may each independently be an integer from 0 to 5, or 0, 1, or 2. For example, xa may be 1 and xb may be 0, but xa and xb are not limited thereto.

R₁₀₁ to R₁₀₈, R₁₁₁ to R₁₁₉ and R₁₂₁ to R₁₂₄ in Formulae 201 and 202 may each independently be:

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group (for example, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, or the like) or a C₁-C₁₀ alkoxy group (for example, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, or the like);

a C₁-C₁₀ alkyl group or a C₁-C₁₀ alkoxy group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, or any combination thereof; or


a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group or a pyrenyl group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group

103

or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, or any combination thereof.


R₁₀₉ in Formula 201 may be a phenyl group, a naphthyl group, an anthracenyl group, or a pyridinyl group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyridinyl group, or any combination thereof.

In one or more embodiments, the compound represented by Formula 201 may be represented by Formula 201A:



R₁₀₁, R₁₁₁, R₁₁₂, and R₁₀₉ in Formula 201A may be understood by referring to the description provided herein.


For example, the hole transport region may include one of Compounds HT1 to HT21 or any combination thereof:




104

-continued

HT2




HT3



105

-continued

HT4



106

-continued

HT6

5

10

15

20

25

30

35

40

HT5




45

50

55

60


65



107

-continued

HT8



5


10

15

20

HT9

25




30

35

40

HT10

45



50

55


60

65


108

-continued


HT11



HT12




HT13



109

-continued

HT14



5


10

15

110


-continued

HT18



HT19

HT15 20




25

30

35


HT16



45


50

HT17




60


65



HT20



HT21




A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes

111

at least one of a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, for example, about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

The hole transport region may further include, in addition to these materials, a charge-generation material for improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

The charge-generation material may be, for example, a p-dopant. The p-dopant may include a quinone derivative, a metal oxide, a cyano group-containing compound, or any combination particular, but embodiments of the present disclosure are not limited thereto. For example, the p-dopant may be: a quinone derivative such as tetracyanoquinodimethane (TCNQ), 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinodimethane (F4-TCNQ), or F6-TCNNQ; metal oxide, such as tungsten oxide and molybdenum oxide; a cyano group-containing compound, such as Compound HT-D1; or any combination thereof.



The hole transport region may include a buffer layer.

Also, the buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, and thus, efficiency of a formed organic light-emitting device may be improved.

Meanwhile, when the hole transport region includes an electron blocking layer, a material for forming the electron


112

blocking layer may include a material that is used in the hole transport region as described above, a host material described below, or any combination thereof. For example, when the hole transport region includes an electron blocking layer, mCP, the Compound HT21, or any combination described below may be used as the material for forming an electron blocking layer.

Then, an emission layer (EML) may be formed on the hole transport region by vacuum deposition, spin coating, casting, LB deposition, or the like. When the emission layer is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied in forming the hole injection layer although the deposition or coating conditions may vary according to a material that is used to form the emission layer.


The emission layer may include a host and a dopant, and the dopant may include the organometallic compound represented by Formula 1 as described herein.

The host may include TPBi, TBADN, ADN (also referred to as "DNA"), CBP, CDBP, TCP, mCP, Compound H50, Compound H51, Compound H52, Compound H53, Compound H54, or any combination thereof:




113


-continued




CBP




CDBP




TCP



mCP



H51



60

114

-continued

H52

5

10

15

20

25

30

35

40


45

H50


50

55


60



H53



H54



65

When the organic light-emitting device is a full-color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and/or a blue emission layer. In one or more embodiments, due to a stacked structure including a red emission layer, a

115

green emission layer, and/or a blue emission layer, the emission layer may emit white light.

When the emission layer includes a host and a dopant, an amount of the dopant may be in a range of about 0.01 parts by weight to about 15 parts by weight based on 100 parts by weight of the host, but embodiments of the present disclosure are not limited thereto.

A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.


Then, an electron transport region may be located on the emission layer.

The electron transport region may include a hole blocking layer, an electron transport layer, an electron injection layer, or any combination thereof.


For example, the electron transport region may have a hole blocking layer/electron transport layer/electron injection layer structure or an electron transport layer/electron injection layer structure. The electron transport layer may have a single-layered structure or a multi-layered structure including two or more different materials.

Conditions for forming the hole blocking layer, the electron transport layer, and the electron injection layer which constitute the electron transport region may be understood by referring to the conditions for forming the hole injection layer.

When the electron transport region includes a hole blocking layer, the hole blocking layer may include, for example, at least one of BCP, Bphen, and BAlq.



BCP





Bphen

In one or more embodiments, the hole blocking layer may include the host, a material for forming an electron transport layer, a material for forming an electron injection layer, which will be described later, or any combination thereof.


A thickness of the hole blocking layer may be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 600 Å. When the thickness of the hole blocking layer is within these ranges, the hole blocking layer may have excellent hole blocking characteristics without a substantial increase in driving voltage.

116


The electron transport layer may include BCP, Bphen, TPBi, Alq₃, BAlq, TAZ, NTAZ, or any combination thereof:

Alq₃

BAlq




TAZ



NTAZ

In one or more embodiments, the electron transport layer may include at least one of Compounds ET1 to ET25 or any combination thereof:

117



ET1


5

10

15

20

ET2




30

35

40

45



ET3

50

55


60

65


118

-continued


ET4



ET5




ET6









119

-continued

**120**


-continued



121

-continued

ET14




5

10

15


20

ET15



40

ET16




65


122

-continued


ET17



ET18




ET19



123

-continued




ET20

5

10

15

20



ET21


25

30

35

40

45



ET22


50

55


60

124


-continued



ET23



ET24



ET25


65 A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. When the thickness of the electron

125


transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.

Also, the electron transport layer may further include, in addition to the materials described above, a metal-containing material.

The metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 or ET-D2:



ET-D1



ET-D2

The electron transport region may include an electron injection layer (EIL) that promotes the flow of electrons from the second electrode **19** thereinto.

The electron injection layer may include LiF, NaCl, CsF, Li₂O, BaO, or any combination thereof.

A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, and, for example, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within the range described above, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

The second electrode **19** may be located on the organic layer **15**. The second electrode **19** may be a cathode. A material for forming the second electrode **19** may be metal, an alloy, an electrically conductive compound, or a combination thereof, which have a relatively low work function. For example, lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) may be used as the material for forming the second electrode **19**. In one or more embodiments, to manufacture a top-emission type light-emitting device, a transmissive electrode formed using ITO or IZO may be used as the second electrode **19**.

Hereinbefore, the organic light-emitting device has been described with reference to FIGURE, but embodiments of the present disclosure are not limited thereto.

According to another aspect, the organic light-emitting device may be included in an electronic apparatus. Thus, an electronic apparatus including the organic light-emitting device is provided. The electronic apparatus may include, for example, a display, an illumination, a sensor, and the like.

Another aspect provides a diagnostic composition including at least one of the organometallic compound represented by Formula 1.

126

The organometallic compound represented by Formula 1 provides high luminescence efficiency. Accordingly, a diagnostic composition including the organometallic compound may have high diagnostic efficiency.

The diagnostic composition may be used in various applications including a diagnosis kit, a diagnosis reagent, a biosensor, and a biomarker.

The term “C₁-C₆₀ alkyl group” as used herein refers to a linear or branched saturated aliphatic hydrocarbons monovalent group having 1 to 60 carbon atoms, and the term “C₁-C₆₀ alkylene group” as used here refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

Examples of the C₁-C₆₀ alkyl group, the C₁-C₂₀ alkyl group, and/or the C₁-C₁₀ alkyl group are a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isohexyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, or a tert-decyl group, each unsubstituted or substituted with a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isohexyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, or any combination thereof. For example, Formula 9-33 is a branched C₆ alkyl group, for example, a tert-butyl group that is substituted with two methyl groups.

The term “C₁-C₆₀ alkoxy group” used herein refers to a monovalent group represented by —OA₁₀₁, (wherein A₁₀₁ is the C₁-C₆₀ alkyl group), and examples thereof are a methoxy group, an ethoxy group, a propoxy group, a butoxy group, and a pentoxy group.

The term “C₂-C₆₀ alkenyl group” as used herein refers to a hydrocarbon group formed by substituting at least one carbon-carbon double bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethenyl group, a propenyl group, and a butenyl group. The term “C₂-C₆₀ alkenylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

The term “C₂-C₆₀ alkynyl group” as used herein refers to a hydrocarbon group formed by substituting at least one carbon-carbon triple bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethynyl group, and a propynyl group. The term “C₂-C₆₀ alkynylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

The term “C₃-C₁₀ cycloalkyl group” as used herein refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms, and the C₃-C₁₀ cycloalkylene group is a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

The term “C₃-C₁₀ cycloalkyl group” as used herein may include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl(norbornanyl) group, a bicyclo[2.2.2]octyl group, and the like.

The term “C₁-C₁₀ heterocycloalkyl group” as used herein refers to a monocyclic group that includes at least one N, O, P, Si, B, Se, Ge, S, or any combination thereof as a ring-forming atom and 1 to 10 carbon atoms, and the C₁-C₁₀ heterocycloalkylene group refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkyl group.

Examples of the C₁-C₁₀ heterocycloalkyl group are a silolanyl group, a silinanyl group, tetrahydrofuranlyl group, a tetrahydro-2H-pyranlyl group, a tetrahydrothiophenyl group, and the like.

The term “C₃-C₁₀ cycloalkenyl group” as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the ring thereof and no aromaticity, and non-limiting examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. The term “C₃-C₁₀ cycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

The term “C₂-C₁₀ heterocycloalkenyl group” as used herein refers to a monovalent monocyclic group that has at least one N, O, P, Si, B, Se, Ge, S, or any combination thereof as a ring-forming atom, 1 to 10 carbon atoms, and at least one carbon-carbon double bond in its ring. Examples of the C₂-C₁₀ heterocycloalkenyl group are a 2,3-dihydrofuranlyl group, and a 2,3-dihydrothiophenyl group. The term “C₂-C₁₀ heterocycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₂-C₁₀ heterocycloalkenyl group.

The term “C₆-C₆₀ aryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and the term “C₆-C₆₀ arylene group” as used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Examples of the C₆-C₆₀ aryl group include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other.

The C₇-C₆₀ alkylaryl group used herein refers to a C₆-C₆₀ aryl group substituted with at least one C₁-C₆₀ alkyl group.

The term “C₁-C₆₀ heteroaryl group” as used herein refers to a monovalent group having at least one hetero atom selected from N, O, P, Si, and S as a ring-forming atom and a cyclic aromatic system having 1 to 60 carbon atoms, and the term “C₁-C₆₀ heteroarylene group” as used herein refers to a divalent group having at least one N, O, P, Si, B, Se, Ge, S, or any combination thereof as a ring-forming atom and a carbocyclic aromatic system having 1 to 60 carbon atoms. Examples of the C₁-C₆₀ heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the rings may be fused to each other.

The C₂-C₆₀ alkyl heteroaryl group used herein refers to a C₁-C₆₀ heteroaryl group substituted with at least one C₁-C₆₀ alkyl group.

The term “C₆-C₆₀ aryloxy group” as used herein indicates —OA₁₀₂ (wherein A₁₀₂ indicates the C₆-C₆₀ aryl group), the

C₆-C₆₀ arylthio group indicates —SA₁₀₃ (wherein A₁₀₃ indicates the C₆-C₆₀ aryl group), and the C₁-C₆₀ alkylthio group indicates —SA₁₀₄ (wherein A₁₀₄ indicates the C₁-C₆₀ alkyl group).

The term “monovalent non-aromatic condensed polycyclic group” as used herein refers to a monovalent group (for example, having 8 to 60 carbon atoms) having two or more rings condensed to each other, only carbon atoms as ring-forming atoms, and no aromaticity in its entire molecular structure. Examples of the monovalent non-aromatic condensed polycyclic group include a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

The term “monovalent non-aromatic condensed heteropolycyclic group” as used herein refers to a monovalent group (for example, having 2 to 60 carbon atoms) having two or more rings condensed to each other, at least one N, O, P, Si, B, Se, Ge, S, or any combination thereof other than carbon atoms, as a ring-forming atom, and no aromaticity in its entire molecular structure. Examples of the monovalent non-aromatic condensed heteropolycyclic group include a carbazolyl group. The term “divalent non-aromatic condensed heteropolycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

The term “C₅-C₃₀ carbocyclic group” as used herein refers to a saturated or unsaturated cyclic group having, as a ring-forming atom, 5 to 30 carbon atoms only. The C₅-C₃₀ carbocyclic group may be a monocyclic group or a polycyclic group. Examples of the “C₅-C₃₀ carbocyclic group (unsubstituted or substituted with at least one R_{1a})” are an adamantane group, a norbornene group, a bicyclo[1.1.1]pentane group, a bicyclo[2.1.1]hexane group, a bicyclo[2.2.1]heptane(norbornane) group, a bicyclo[2.2.2]octane group, a cyclopentane group, a cyclohexane group, a cyclohexene group, a benzene group, a naphthalene group, an anthracene group, a phenanthrene group, a triphenylene group, a pyrene group, a chrysene group, a 1,2,3,4-tetrahydronaphthalene group, a cyclopentadiene group, a silole group, a fluorene group (each unsubstituted or substituted with at least one R_{1a}).

The term “C₁-C₃₀ heterocyclic group” as used herein refers to a saturated or unsaturated cyclic group having, as a ring-forming atom, at least one N, O, P, Si, Se, Ge, B, S, or any combination thereof other than 1 to 30 carbon atoms. The C₁-C₃₀ heterocyclic group may be a monocyclic group or a polycyclic group. The “C₁-C₃₀ heterocyclic group (unsubstituted or substituted with at least one R_{1a})” may be, for example, a thiophene group, a furan group, a pyrrole group, a silole group, borole group, a phosphole group, a selenophene group, a germole group, a benzothiophene group, a benzofuran group, an indole group, an indene group, a benzosilole group, a benzoborole group, a benzophosphole group, a benzoselenophene group, a benzogermole group, a dibenzothiophene group, a dibenzofuran group, a carbazole group, a dibenzosilole group, a dibenzoborole group, a dibenzophosphole group, a dibenzoselenophene group, a dibenzogermole group, a dibenzothiophene 5-oxide group, a 9H-fluorene-9-one group, a dibenzothiophene 5,5-dioxide group, an azabenzothiophene group, an azabenzofuran group, an azaindole group, an azaindene group, an azabenzosilole group, an azabenzoborole group, an azabenzophosphole group, an azabenzoselenophene group, an azabenzogermole group, an azadibenzothiophene group, an azadibenzofuran group, an azacarbazole group, an

azafluorene group, an azadibenzosilole group, an azadibenzoborole group, an azadibenzophosphole group, an azadibenzoselenophene group, an azadibenzogermole group, an azadibenzothiophene 5-oxide group, an aza-9H-fluorene-9-one group, an azadibenzothiophene 5,5-dioxide group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a phenanthroline group, a pyrazole group, an imidazole group, a triazole group, an oxazole group, an isooxazole group, a thiazole group, an isothiazole group, an oxadiazole group, a thiadiazole group, a benzopyrazole group, a benzimidazole group, a benzoxazole group, a benzothiazole group, a benzoxadiazole group, a benzothiadiazole group, a 5,6,7,8-tetrahydroisoquinoline group, or a 5,6,7,8-tetrahydroquinoline group (each unsubstituted or substituted with at least one R_{1a}).

The terms “fluorinated C_1 - C_{60} alkyl group (or a fluorinated C_1 - C_{20} alkyl group or the like)”, “fluorinated C_3 - C_{10} cycloalkyl group”, “fluorinated C_1 - C_{10} heterocycloalkyl group”, and “fluorinated phenyl group” respectively indicate a C_1 - C_{60} alkyl group (or a C_1 - C_{20} alkyl group or the like), a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, and a phenyl group, each substituted with at least one fluoro group ($-F$). For example, the “fluorinated C_1 alkyl group (that is, the fluorinated methyl group)” may include $-CF_3$, $-CF_2H$, and $-CFH_2$. The “fluorinated C_1 - C_{60} alkyl group (or, a fluorinated C_1 - C_{20} alkyl group, or the like)”, “the fluorinated C_3 - C_{10} cycloalkyl group”, “the fluorinated C_1 - C_{10} heterocycloalkyl group”, or “the fluorinated a phenyl group” may be i) a fully fluorinated C_1 - C_{60} alkyl group (or, a fully fluorinated C_1 - C_{20} alkyl group, or the like), a fully fluorinated C_3 - C_{10} cycloalkyl group, a fully fluorinated C_1 - C_{10} heterocycloalkyl group, or a fully fluorinated phenyl group, wherein, in each group, all hydrogen included therein is substituted with a fluoro group, or ii) a partially fluorinated C_1 - C_{60} alkyl group (or, a partially fluorinated C_1 - C_{20} alkyl group, or the like), a partially fluorinated C_3 - C_{10} cycloalkyl group, a partially fluorinated C_1 - C_{10} heterocycloalkyl group, or partially fluorinated phenyl group, wherein, in each group, all hydrogen included therein is not substituted with a fluoro group.

The terms “deuterated C_1 - C_{60} alkyl group (or a deuterated C_1 - C_{20} alkyl group or the like)”, “deuterated C_3 - C_{10} cycloalkyl group”, “deuterated C_1 - C_{10} heterocycloalkyl group”, and “deuterated phenyl group” respectively indicate a C_1 - C_{60} alkyl group (or a C_1 - C_{20} alkyl group or the like), a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, and a phenyl group, each substituted with at least one deuterium. For example, the “deuterated C_1 alkyl group (that is, the deuterated methyl group)” may include $-CD_3$, $-CD_2H$, and $-CDH_2$, and examples of the “deuterated C_3 - C_{10} cycloalkyl group” are, for example, Formula 10-501 and the like. The “deuterated C_1 - C_{60} alkyl group (or, the deuterated C_1 - C_{20} alkyl group or the like)”, “the deuterated C_3 - C_{10} cycloalkyl group”, “the deuterated C_1 - C_{10} heterocycloalkyl group”, or “the deuterated phenyl group” may be i) a fully deuterated C_1 - C_{60} alkyl group (or, a fully deuterated C_1 - C_{20} alkyl group or the like), a fully deuterated C_3 - C_{10} cycloalkyl group, a fully deuterated C_1 - C_{10} heterocycloalkyl group, or a fully deuterated phenyl group, in which, in each group, all hydrogen included therein are substituted with deuterium, or ii) a partially deuterated C_1 - C_{60} alkyl group (or, a partially deuterated C_1 - C_{20} alkyl group or the like), a partially deuterated C_3 - C_{10} cycloalkyl group, a partially deuterated C_1 - C_{10} heterocycloalkyl group, or a partially

deuterated phenyl group, in which, in each group, all hydrogens included therein are not substituted with deuterium.

The term “(C_1 - C_{20} alkyl) ‘X’ group” as used herein refers to a ‘X’ group that is substituted with at least one C_1 - C_{20} alkyl group. For example, the term “(C_1 - C_{20} alkyl) C_3 - C_{10} cycloalkyl group” as used herein refers to a C_3 - C_{10} cycloalkyl group substituted with at least one C_1 - C_{20} alkyl group, and the term “(C_1 - C_{20} alkyl)phenyl group” as used herein refers to a phenyl group substituted with at least one C_1 - C_{20} alkyl group. An example of a (C_1 alkyl) phenyl group is a tolyl group.

The terms “an azaindole group, an azabenzoborole group, an azabenzophosphole group, an azaindene group, an azabenzosilole group, an azabenzogermole group, an azabenzothiophene group, an azabenzoselenophene group, an azabenzofuran group, an azacarbazole group, an azadibenzoborole group, an azadibenzophosphole group, an azafluorene group, an azadibenzosilole group, an azadibenzogermole group, an azadibenzothiophene group, an azadibenzoselenophene group, an azadibenzofuran group, an azadibenzothiophene 5-oxide group, an aza-9H-fluorene-9-one group, and an azadibenzothiophene 5,5-dioxide group” respectively refer to heterocyclic groups having the same backbones as “an indole group, a benzoborole group, a benzophosphole group, an indene group, a benzosilole group, a benzogermole group, a benzothiophene group, a benzoselenophene group, a benzofuran group, a carbazole group, a dibenzoborole group, a dibenzophosphole group, a fluorene group, a dibenzosilole group, a dibenzogermole group, a dibenzothiophene group, a dibenzoselenophene group, a dibenzofuran group, a dibenzothiophene 5-oxide group, a 9H-fluorene-9-one group, a dibenzothiophene group, and a 5,5-dioxide group,” in which, in each group, at least one carbon selected from ring-forming carbons is substituted with nitrogen.

At least one substituent of the substituted C_5 - C_{30} carbocyclic group, the substituted C_2 - C_{30} heterocyclic group, the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_1 - C_{60} alkoxy group, the substituted C_1 - C_{60} alkylthio group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_1 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_2 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the substituted C_7 - C_{60} alkylaryl group, the substituted C_6 - C_{60} aryloxy group, the substituted C_6 - C_{60} arylthio group, the substituted C_1 - C_{60} heteroaryl group, the substituted C_2 - C_{60} alkyl heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may each independently be:

deuterium, $-F$, $-Cl$, $-Br$, $-I$, $-CD_3$, $-CD_2H$, $-CDH_2$, $-CF_3$, $-CF_2H$, $-CFH_2$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, or a C_1 - C_{60} alkylthio group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, or a C_1 - C_{60} alkylthio group, substituted with deuterium, $-F$, $-Cl$, $-Br$, $-I$, $-CD_3$, $-CD_2H$, $-CDH_2$, $-CF_3$, $-CF_2H$, $-CFH_2$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a

131

sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₇-C₆₀ alkyl aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a C₂-C₆₀ alkyl heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), —Ge(Q₁₃)(Q₁₄)(Q₁₅), —B(Q₁₆)(Q₁₇), —P(=O)(Q₁₈)(Q₁₉), —P(Q₁₈)(Q₁₉), or any combination thereof;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₇-C₆₀ alkyl aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a C₂-C₆₀ alkyl heteroaryl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₁-C₆₀ alkylthio group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₇-C₆₀ alkyl aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a C₂-C₆₀ alkyl heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), —Ge(Q₂₃)(Q₂₄)(Q₂₅), —B(Q₂₆)(Q₂₇), —P(=O)(Q₂₈)(Q₂₉), —P(Q₂₈)(Q₂₉), or any combination thereof;

—N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), —Ge(Q₃₃)(Q₃₄)(Q₃₅), —B(Q₃₆)(Q₃₇), —P(=O)(Q₃₈)(Q₃₉), or —P(Q₃₈)(Q₃₉); or any combination thereof.

Q₁ to Q₉, Q₁₁ to Q₁₉, Q₂₁ to Q₂₉, and Q₃₁ to Q₃₉ described herein may each independently be: hydrogen; deuterium; —F; —Cl; —Br; —I; a hydroxyl group; a cyano group; a nitro group; an amidino group; a hydrazine

132

group; a hydrazone group; a carboxylic acid group or a salt thereof; a sulfonic acid group or a salt thereof; a phosphoric acid group or a salt thereof; a C₁-C₆₀ alkyl group which is unsubstituted or substituted with deuterium, a C₁-C₆₀ alkyl group, a C₆-C₆₀ aryl group, or any combination thereof; a C₂-C₆₀ alkenyl group; a C₂-C₆₀ alkynyl group; a C₁-C₆₀ alkoxy group; a C₁-C₆₀ alkylthio group; a C₃-C₁₀ cycloalkyl group; a C₁-C₁₀ heterocycloalkyl group; a C₃-C₁₀ cycloalkenyl group; a C₂-C₁₀ heterocycloalkenyl group; a C₆-C₆₀ aryl group which is unsubstituted or substituted with deuterium, a C₁-C₆₀ alkyl group, a C₆-C₆₀ aryl group, or any combination thereof; a C₆-C₆₀ aryloxy group; a C₆-C₆₀ arylthio group; a C₁-C₆₀ heteroaryl group; a monovalent non-aromatic condensed polycyclic group; or a monovalent non-aromatic condensed heteropolycyclic group.

For example, Q₁ to Q₉, Q₁₁ to Q₁₉, Q₂₁ to Q₂₉, and Q₃₁ to Q₃₉ described herein may each independently be:


—CH₃, —CD₃, —CD₂H, —CDH₂, —CH₂CH₃, —CH₂CD₃, —CH₂CD₂H, —CH₂CDH₂, —CHDCD₃, —CHDCD₂H, —CHDCDH₂, —CHDCD₃, —CD₂CD₃, —CD₂CD₂H, or —CD₂CDH₂; or

an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, a phenyl group, a biphenyl group, or a naphthyl group, each unsubstituted or substituted with deuterium, a C₁-C₁₀ alkyl group, a phenyl group, or any combination thereof.

Hereinafter, a compound and an organic light-emitting device according to embodiments are described in detail with reference to Synthesis Example and Examples. However, the organic light-emitting device is not limited thereto. The wording "B was used instead of A" used in describing Synthesis Examples means that an amount of A used was identical to an amount of B used, in terms of a molar equivalent.



EXAMPLES

Synthesis Example 1 (Compound 1)



133

134



Synthesis of Intermediate 1-1


Ligand 1 (1.1 g, 3.1 mmol) and 0.5 g (1.5 mmol) of iridium chloride were mixed with 30 mL of ethoxyethanol and 10 mL of distilled water, and then the mixture was heated and refluxed for 16 hours. When the reaction was completed, the temperature was cooled to room temperature, and a solid material formed therefrom was filtered and washed thoroughly with water, methanol, and hexane in the stated order. An obtained solid was recrystallized, and then filtered and dried in a vacuum oven to obtain 0.72 g of Intermediate 1-1.

Synthesis of Compound 1

0.72 g (0.38 mmol) of Intermediate 1-1, 0.5 g (2.3 mmol) of 3,7-diethylnonane-4,6-dione, and 0.24 g (2.3 mmol) of Na_2CO_3 were mixed with 25 mL of ethoxyethanol, and then refluxed at 90°C . for 18 hours for reaction. When the reaction is completed, the temperature was cooled to room temperature, and a solid material formed therefrom was filtered and purified by liquid chromatography to obtain 0.7 g (yield of 82%) Compound 1. Compound 1 was identified by LC-MS.


LC-MS $m/z=1114(\text{M}^+\text{H}^+)$

Synthesis Example 2 (Compound 2)



135


136



0.4 g (yield of 47%) of Compound 2 was obtained by using the same method as the synthesis method of Compound 1 of Synthesis Example 1, except that 3,7-diethyl-5-methylnonane-4,6-dione was used instead of 3,7-diethyl-
 nonane-4,6-dione. Compound 2 was identified by LC-MS.

LC-MS $m/z=1128(M^+H)^+$

Synthesis Example 3 (Compound 3)



137

Synthesis of Intermediate 3-1

0.7 g of Intermediate 3-1 was obtained by using the same method as the synthesis method of Intermediate 1-1 of Synthesis Example 1, except that Ligand 3 was used instead of Ligand 1.

Synthesis of Compound 3


0.6 g (yield of 70%) of Compound 3 was obtained by using the same method as the synthesis method of Com-

138

pound 1 of Synthesis Example 1, except that Intermediate 3-1 was used instead of Intermediate 1-1. Compound 3 was identified by LC-MS.

LC-MS $m/z=1150(M^+H)^+$

Synthesis Example 4 (Compound 4)



139

Synthesis of Intermediate 4-1

0.6 g of Intermediate 4-1 was obtained by using the same method as the synthesis method of Intermediate 1-1 of Synthesis Example 1, except that Ligand 4 was used instead of Ligand 1.

Synthesis of Compound 4




0.6 g (yield of 68%) of Compound 4 was obtained by using the same method as the synthesis method of Com-

140

pound 1 of Synthesis Example 1, except that Intermediate 4-1 was used instead of Intermediate 1-1. Compound 4 was identified by LC-MS.

LC-MS $m/z=1270(M^+H)^+$

Synthesis Example 5 (Compound 5)



141

Synthesis of Intermediate 5-1



0.7 g of Intermediate 5-1 was obtained by using the same method as the synthesis method of Intermediate 1-1 of Synthesis Example 1, except that Ligand 5 was used instead of Ligand 1.

Synthesis of Compound 5

0.5 g (yield of 59%) of Compound 5 was obtained by using the same method as the synthesis method of Compound 1 of Synthesis Example 1, except that Intermediate 5-1 was used instead of Intermediate 1-1. Compound 5 was identified by LC-MS.

LC-MS $m/z=1275(M^+H)^+$

Synthesis Example 6 (Compound 6)

**142**


Synthesis of Intermediate 6-1

0.7 g of Intermediate 6-1 was obtained by using the same method as the synthesis method of Intermediate 1-1 of Synthesis Example 1, except that Ligand 6 was used instead of Ligand 1.

Synthesis of Compound 6

0.6 g (yield of 80%) of Compound 6 was obtained by using the same method as the synthesis method of Compound 1 of Synthesis Example 1, except that Intermediate 6-1 was used instead of Intermediate 1-1. Compound 6 was identified by LC-MS.

LC-MS $m/z=1186(M^+H)^+$



16

0.6 g (yield of 67%) of Compound 16 was obtained by using the same method as the synthesis method of Compound 3 of Synthesis Example 3, except that 3,3,7,7-tetramethylnonane-4,6-dione was used instead of 3,7-diethylnonane-4,6-dione. Compound 16 was identified by LC-MS.

LC-MS $m/z=1150(M+H)^+$

Evaluation Example 1: Evaluation of HOMO and LUMO Energy Level

According to the method of Table 2, HOMO and LUMO energy levels of Compounds 1 to 6 and 16 were evaluated, and results thereof are shown in Table 3.

TABLE 2


HOMO energy level evaluation method	1) Differential pulse voltammetry (DPV) (electrolyte: 0.1M Bu_4NPF_6 in MC, Pulse height: 50 mV, Pulse width: 1 sec, Step height: 10 mV, Step width: 2 sec, scan rate: 5 mV/sec, reference electrode: Ag/AgNO ₃) is used to obtain a potential(V)-current(mA) graph of each Compound, and then E_{peak} (eV) which is an oxidation peak potential of the graph is evaluated (here, when a HOMO energy range exceeds a solvent window, a solvent is changed for measurement). 2) E_{peak} (eV) is substituted for E_{peak} in the equation of $HOMO(eV) = -4.8 - (E_{peak} - E_{peak}(Ferrocene))$ to evaluate HOMO energy level (eV) of each Compound.
LUMO energy level evaluation method	1) Differential pulse voltammetry (DPV) (electrolyte: 0.1M Bu_4NPF_6 in dimethylformamide, Pulse height: 50 mV, Pulse width: 1 sec, Step height: 10 mV, Step width: 2 sec, scan rate: 5 mV/sec, reference electrode: Ag/AgNO ₃) is used to obtain a potential(V)-current(mA) graph of each Compound, and then E_{peak} (eV) which is a reduction peak potential of the graph is evaluated (here, when a LUMO energy range exceeds a solvent window, a solvent is changed for measurement).

TABLE 2-continued

2) E_{peak} (eV) is substituted for E_{peak} in the equation of $LUMO(eV) = -4.8 - (E_{peak} - E_{peak}(Ferrocene))$ to evaluate LOMO energy level (eV) of each Compound.


TABLE 3




Compound No.	HOMO DPV (eV)	LUMO DPV (eV)
1	-5.10	-2.46
2	-5.04	-2.44
3	-5.14	-2.55
4	-5.17	-2.61
5	-5.15	-2.59
6	-5.15	-2.61
16	-5.11	-2.53



145



TABLE 3-continued

Compound No.	HOMO DPV (eV)	LUMO DPV (eV)
		
2		



146

TABLE 3-continued

Compound No.	HOMO DPV (eV)	LUMO DPV (eV)
		
6		
		
16		

Referring to Table 3, it is confirmed that Compounds 1 to 6 and 16 have excellent electrical characteristics.

Evaluation Example 2: Decay Time Measurement

A quartz substrate washed by using chloroform and pure water was prepared, and then a predetermined material shown in Table 4 was vacuum(co)-deposited at a vacuum pressure of 10^{-7} torr to prepare Films 1 to 6 and 16 each having a thickness of 50 nm.

Subsequently, PL spectrum of each of Films 1 to 6 and 16 was evaluated at room temperature by using TRPL measurement system FluoTime 300 manufactured by PicoQuant and a pumping source PLS340 manufactured by PicoQuant (excitation wavelength=340 nm, spectral width=20 nm), and then the wavelength of main 340 repeated the measure of the number of photons emitted from each Film at the main peak by a photon pulse (pulse width=500 picoseconds) applied to each Film according to the time, based on time-correlated single photon counting (TCSPC), thereby obtaining a sufficiently fittable TRPL curve. Two or more exponential decay functions were fitted to the result obtained therefrom, thereby obtaining $T_{decay}(Ex)$, that is, decay time, of each of Films 1 to 6 and 16 and results thereof are shown in Table 4. A function for fitting is as shown in Equation 1, and from among T_{decay} values obtained from each exponential decay function used for fitting, the largest T_{decay} was obtained as $T_{decay}(Ex)$. In this regard, the same measurement was performed during the same measurement time as that for obtaining TRPL curve in the dark state (in which pumping signals entering a film are blocked) to obtain a baseline or a background signal curve for use as a baseline for fitting.


147

$$f(t) = \sum_{i=1}^n A_i \exp(-t/T_{decay,i})$$

Equation 1

TABLE 4

Film no.	Compound used in film production	Decay time (μs)
1	Compound H52:Compound 1 (weight ratio of 98:2)	0.68
2	Compound H52:Compound 2 (weight ratio of 98:2)	0.63
3	Compound H52:Compound 3 (weight ratio of 98:2)	0.63
4	Compound H52:Compound 4 (weight ratio of 98:2)	0.78
5	Compound H52:Compound 5 (weight ratio of 98:2)	0.78
6	Compound H52:Compound 6 (weight ratio of 98:2)	0.73
16	Compound H52:Compound 16 (weight ratio of 98:2)	0.64



H52

Referring to Table 4, Compounds 1 to 6 and 16 have relatively small decay time characteristics.

Evaluation Example 3: Horizontal Orientation Ratio (Optical Orientation Ratio)

In a vacuum deposition apparatus having a vacuum pressure of 1×10^{-7} torr, Compound H52 and Compound 1 were co-deposited at a weight ratio of 98:2 on a fused silica layer (thickness: 1 mm) to form a film having a thickness of 40 nm, and then sealed with glass and glue under a nitrogen atmosphere.

Meanwhile, an angle-dependent PL measurement apparatus having the same structure as that shown in FIG. 3 of Korean Patent Application Publication No. 2013-0150834 was prepared. Detail specifications are as follows:

Excitation-light wavelength: 325 nm

Source of excitation-light: He—Cd laser of Melles Griot Inc.

Excitation-light irradiation member: optical fiber having a diameter of 1 mm of Thorlabs Inc.

Semi-cylindrical prism: a fused silica having a diameter of 100 mm and a length of 30 mm

Emitted-light detection member: photomultiplier tube of Acton Inc.

Polarizer mounted on emitted-light detection member: linear polarizer of Thorlabs Inc.

Recorder: SpectraSense of Acton Inc.

Incidence angle of excitation light: $\theta_P = 45^\circ$, $\theta_H = 0^\circ$

148

Distance from a sample to the emitted-light detection member (or a radius of a movement path of the emitted-light detection member): 900 mm


Subsequently, the film was fixed on a semi-cylindrical lens and irradiated with 325 nm laser to emit light. The emitted light passed through a polarization film, and then, in order to measure a p-polarized photoluminescence intensity with respect to light in a Max wavelength of a spectrum in a range of 90 degree to 0 degree, the semi-cylindrical lens, on which the sample was fixed, was rotated by 1 degree with respect to an axis of the semi-cylindrical lens by using a charge-coupled device (CCD).

The p-polarized photoluminescence intensity (a first p-polarized photoluminescence intensity) in a case where each compound is vertically aligned and the p-polarized photoluminescence intensity (a second p-polarized photoluminescence intensity) in a case where each compound is horizontally aligned were respectively calculated within a range of 0 to 90 degrees. The p-polarized photoluminescence intensity obtained by multiplying the first p-polarized photoluminescence intensity and the second p-polarized photoluminescence intensity respectively by a weight value was obtained to obtain a weight value corresponding to the measured p-polarization photoluminescence intensity. Then, the horizontal orientation ratio of each compound shown in Table 5 was measured and results thereof are shown in Table 5. Here, the angle-dependent photoluminescence spectrum was analyzed using a classical dipole model which regards light emitted from excitons as dissipated power from an oscillating dipole, and the horizontal orientation ratio for Compound 1 was evaluated.

This was performed on each of Compounds 2 to 6, 16 and A and results thereof are shown in Table 5.

TABLE 5

Co-deposition material	Horizontal orientation ratio (optical orientation ratio) (%)
H52: Compound 1 (2 wt %)	94
H52: Compound 2 (2 wt %)	93
H52: Compound 3 (2 wt %)	93
H52: Compound 4 (2 wt %)	92
H52: Compound 5 (2 wt %)	94
H52: Compound 6 (2 wt %)	94
H52: Compound 16 (2 wt %)	93
H52: Compound A (2 wt %)	87



A

Referring to Table 5, it is confirmed that Compounds 1 to 6 and 16 have excellent optical orientation ratios, compared with Compound A. Example 1-1 (deposition process)



As an anode, an ITO-patterned glass substrate was cut to a size of 50 mm×50 mm×0.5 mm, sonicated with isopropyl alcohol and pure water each for 5 minutes, and then cleaned by exposure to ultraviolet rays and ozone for 30 minutes. The resultant glass substrate was loaded onto a vacuum deposition apparatus.

149

On the ITO anode, HT3 and F6TCNNQ were vacuum-codeposited at a weight ratio of 98:2 to form a hole injection layer having a thickness of 100 Å, HT3 was vacuum-deposited on the hole injection layer to form a hole transport layer having a thickness of 1,350 Å, and HT21 was vacuum-deposited on the hole transport layer to form an electron blocking layer having a thickness of 300 Å.

Subsequently, H52 (host) and Compound 1 (dopant) were co-deposited at a weight ratio of 98:2 on the electron blocking layer to form an emission layer having a thickness of 400 Å.


Thereafter, ET3 and ET-D1 were co-deposited at a volume ratio of 50:50 on the emission layer to form an electron transport layer having a thickness of 350 Å, ET-D1 was vacuum-deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Al was vacuum-deposited on the electron injection layer to form a cathode having a thickness of 1,000 Å, thereby completing the manufacture of an organic light-emitting device having a structure of ITO (1,500 Å)/HT3+F6TCNNQ (2 wt %) (100 Å)/HT3 (1350 Å)/HT21 (300 Å)/H52+Compound 1 (2 wt %) (400 Å)/ET3+ET-D1 (50%) (350 Å)/ET-D1 (10 Å)/Al (1,000 Å).




150

-continued


HT21




H52



ET3



ET-D1



151

Examples 1-2 to 1-7 and Comparative Example 1-A

Organic light-emitting devices were manufactured in the same manner as in Example 1-1, except that Compounds shown in Tables 6 and 7 were each used instead of Compound 1 as a dopant in forming an emission layer.

Evaluation Example 4: Characteristics Evaluation of Organic Light-Emitting Device (Deposition Process)

The driving voltage, current density, current efficiency, external quantum efficiency (EQE), roll-off ratio, emission

152

peak wavelength of an EL spectrum, full width at half maximum (FWHM) of an EL spectrum, and CIE x coordinate of each organic light-emitting device manufactured according to Examples 1-1 to 1-7 and Comparative Examples 1-A were evaluated, and results thereof were shown in Tables 6 and 7. As evaluation apparatuses, a current-voltage meter (Keithley 2400) and a luminance meter (Minolta Cs-1000A) were used. The roll-off ratio was calculated according to Equation 20 below.


$$\text{Roll off ratio} = \{1 - (\text{efficiency(at 3500 nit)/maximum emission efficiency})\} \times 100\% \quad \text{Equation 20}$$

TABLE 6


	Dopant Compound No.	Driving Voltage Voltage (V)	Current density (mA/cm ²)	Max Current efficiency (cd/A)	Max EQE (%)	Roll-off ratio (%)	Maximum emission wavelength (nm)	FWHM (nm)	Color coordinate (CIE _x)
Example 1-1	1	4.49	8.89	42.4	32.7	7	614	46.54	0.656
Comparative Example 1-A	A	4.80	10.19	37.4	27.8	8	612	60.00	0.647

TABLE 7

	Dopant Compound No.	Driving Voltage Voltage (V)	Current density (mA/cm ²)	Max Current efficiency (cd/A)	Max EQE (%)	Roll-off ratio (%)	Maximum emission wavelength (nm)	FWHM (nm)	Color coordinate (CIE _x)
Example 1-2	2	4.56	9.72	27.6	31.7	10	623	51.93	0.675
Example 1-3	3	4.63	9.14	28.8	32.0	12	622	49.36	0.670
Example 1-4	4	4.45	8.80	23.4	28.1	13	624	49.01	0.667
Example 1-5	5	4.56	9.89	24.1	30.7	12	627	50.00	0.672
Example 1-6	6	4.89	10.02	21.6	31.1	13	630	50.97	0.677
Example 1-7	16	4.58	9.02	26.6	32.6	12	623	49.82	0.673



1



2

TABLE 7-continued







	Dopant Compound No.	Driving Voltage Voltage (V)	Current density (mA/cm ²)	Max Current efficiency (cd/A)	Max EQE (%)	Roll- off ratio (%)	Maximum emission wavelength (nm)	FWHM (nm)	Color coordinate (CIEx)
		3							
		4							
		5							
		6							

TABLE 7-continued

Dopant Compound No.	Driving Voltage Voltage (V)	Current density (mA/cm ²)	Max Current efficiency (cd/A)	Max EQE (%)	Roll- off ratio (%)	Maximum emission wavelength (nm)	FWHM (nm)	Color coordinate (CIEx)
								
16								
								
A								

From Table 6, it is confirmed that a maximum emission wavelength of the organic light-emitting device manufactured according to Example 1-1 is similar to a maximum emission wavelength of the organic light-emitting device manufactured according to Comparative Example 1-A, and the organic light-emitting device manufactured according to Example 1-1 emits red light having excellent color purity and a relatively narrow FWHM and has excellent driving voltage, excellent current density, excellent current efficiency, excellent EQE, and excellent roll-off ratio, compared to the organic light-emitting device manufactured according to Comparative Example 1-A.

Additionally, from Table 7, it is confirmed that organic light-emitting devices manufactured according to Examples 1-2 to 1-7 emit red light having excellent color purity, a relatively narrow FWHM, and a maximum emission wavelength having 620 nm or more and have excellent driving voltage, excellent current density, excellent current efficiency, excellent EQE, and excellent roll-off ratio.

Example 2-1 (Solution Process)

As an anode, a hydrophobic pixel-defining pattern was formed on a glass substrate on which ITO was deposited to a thickness of 1,500 Å, cut to a size of 50 mm×50 mm×0.5 mm, sonicated using isopropyl alcohol and pure water each for 5 minutes, and then cleaned by exposure to ultraviolet rays and ozone for 1 minute.

On the ITO anode, 25 pl of HIL ink (PEDOT/PSS, CLEVIOS P JET 700N available from Heraeus) was provided using inkjet process and then dried in a vacuum condition, and baked for 15 minutes at 230° C. under air by using a hot plate to remove residual solvent therefrom, thereby forming a hole injection layer having a thickness of 150 Å.

On the hole injection layer, 90 pl of HTL ink (TFB, ADS259BE available from American Dye Source) was provided using inkjet process and then dried in a vacuum condition, and baked for 30 minutes at 230° C. under N₂ atmosphere by using a hot plate to remove residual solvent therefrom, thereby forming a hole transport layer having a thickness of 800 Å.

On the hole transport layer, 60 pl of EML ink (wherein methylbenzoate is included as a solvent, a total amount of a host and a dopant is 1 wt % per 100 wt % of EML ink, and a host and a dopant are mixed at a weight ratio of 95:5) including a mixture of Compound H53 and H54 (host) and Compound 1 (dopant) was provided using an inkjet process and then dried in a vacuum condition, and baked for 10 minutes at 130° C. under N₂ atmosphere by using a hot plate to remove residual solvent therefrom, thereby forming an emission layer having a thickness of 400 Å.

BCP was vacuum-deposited on the emission layer to form a hole blocking layer having a thickness of 50 Å, Alq₃ was vacuum-deposited on the hole blocking layer to form an electron transport layer having a thickness of 350 Å, LiF was vacuum-deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Mg and Ag were co-deposited at a weight ratio of 90:10 on the electron injection layer to form a cathode having a thickness of 120 Å, thereby completing the manufacture of an organic light-emitting device (emitting red light).

Comparative Example 2-A

An organic light-emitting device was manufactured in the same manner as in Example 2-1, except that Compound A was used instead of Compound 1 as a dopant in forming an emission layer.


157

Evaluation Example 5: Characteristic Evaluation of Organic Light-Emitting Device (Solution Process)


The driving voltage, current efficiency, external quantum efficiency (EQE), emission peak wavelength of an EL spectrum, full width at half maximum (FWHM) of an EL spectrum, and CIE x coordinate of each organic light-emitting device manufactured according to Example 2-1 and Comparative Example 2-A were evaluated using the same method as the method described in Evaluation Example 4, and results thereof are shown in Table 8.

TABLE 8

	Do- pant Com- pound No.	Driv- ing Vol- tage Vol- tage (V)	Current Efficien- cy (cd/A)	Max EQE (%)	Maximum emission wave- length (nm)	FWHM (nm)	Color co- ordinate (CIE _x)
Example 2-1	1	8.0	15.5	15.12	617	47.0	0.665
Compara- tive Example 2-A	A	8.2	14.7	13.07	616	57.4	0.661



1



A

From Table 8, it is confirmed that organic light-emitting device manufactured according to Example 2-1 emit red light having excellent color purity and a relatively narrow FWHM and have excellent driving voltage, excellent current density, excellent current efficiency, excellent EQE, and excellent roll-off ratio, compared to organic light-emitting devices manufactured according to Comparative Example 2-A.

The organometallic compound has excellent electrical characteristics and stability. Thus, electronic device including the organometallic compound, for example, an organic light-emitting device, may have improved driving voltage, improved current efficiency, improved EQE, improved roll-off ratio, and a FWHM of an emission peak of a relatively narrow EL spectrum. Accordingly, a high-quality organic

158


light-emitting device and electronic apparatus including the same may be implemented by using the organometallic compound.

It should be understood that embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments. While one or more embodiments have been described with reference to the FIGURES, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope as defined by the following claims.


What is claimed is:

1. An organometallic compound represented by Formula 1 below:


Formula 1



wherein, in Formula 1,
Y₂ is C,
a group represented by









in Formula 1 is a group represented by one of Formulae A(1) to A(10),



159

-continued



160

-continued

A(2)

A(8)

5

A(3)

10

15

A(4)

20

25

A(5)

30

35

40

A(6)

45




50

A(7)

55

60

65



wherein,

R₁₀ and R₁₂ in Formula A(1) are hydrogen,

R₉ and R₁₁ in Formula A(1) are each independently a group represented by Formula 2-2, deuterium, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₁-C₆₀ alkylthio group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

X₂₁ in Formulae A(6) to A(10) is O, S, N(R₂₅), or Si(R₂₅)(R₂₆),

R₉ to R₁₂ and R₂₁ to R₂₆ in Formulae A(2) to A(10) are each independently a group represented by Formula 2-2, hydrogen, deuterium, —F, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₁-C₆₀ alkylthio group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substi-

161

tuted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, provided that, i) at least one of R₉, R₁₀, R₂₁ and R₂₄ in Formula A(2) is not hydrogen, ii) at least one of R₉, R₁₂, R₂₁ and R₂₄ in Formula A(3) is not hydrogen, and iii) at least one of R₁₁, R₁₂, R₂₁ and R₂₄ in Formula A(4) is not hydrogen,

*[†] in Formulae A(1) to A(10) is a binding site to Ir in Formula 1, and

*^{††} in Formulae A(1) to A(10) is a binding site to a neighboring atom in Formula 1,

R₁ to R₈, and A₁ to A₇ are each independently a group represented by Formula 2-1, a group represented by Formula 2-2, hydrogen, deuterium, —F, —Cl, —Br, —I, —SF₅, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₁-C₆₀ alkylthio group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —B(Q₆)(Q₇), —P(=O)(Q₈)(Q₉), or —P(Q₈)(Q₉),

*—Si(Z₁)(Z₂)(Z₃)

Formula 2-1

*—Ge(Z₁₁)(Z₁₂)(Z₁₃)

Formula 2-2

Z₁ to Z₃ and Z₁₁ to Z₁₃ in Formulae 2-1 and 2-2 are each independently hydrogen, deuterium, —F, —Cl, —Br, —I, —SF₅, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₁-C₆₀ alkylthio group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a

162

substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), —Ge(Q₃)(Q₄)(Q₅), —B(Q₆)(Q₇), —P(=O)(Q₈)(Q₉) or —P(Q₈)(Q₉), and * indicates a binding site to a neighboring atom,

a₂ is an integer of 0 to 20, wherein, when a₂ is 2 or more, two or more of R₂₀(s) are identical to or different from each other,

at least one of R₃ to R₆ is independently a group represented by Formula 2-1 or a group represented by Formula 2-2,

two or more of R₁ to R₈ are optionally linked together to form a C₅-C₃₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C₁-C₃₀ heterocyclic group unsubstituted or substituted with at least one R_{1a},

two or more R₉ to R₁₂ and R₂₁ to R₂₆ in Formulae A(2) to A(10) are optionally linked together to form a C₅-C₃₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C₁-C₃₀ heterocyclic group unsubstituted or substituted with at least one R_{1a},

two or more of A₁ to A₇ are optionally linked together to form a C₅-C₃₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C₁-C₃₀ heterocyclic group unsubstituted or substituted with at least one R_{1a},

R_{1a} is the same as described in connection with A₇, and

a substituent of the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₁-C₆₀ alkylthio group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₂-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is:

deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, or a C₁-C₆₀ alkylthio group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, or a C₁-C₆₀ alkylthio group, each substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic con-

163

densed heteropolycyclic group, $-\text{N}(\text{Q}_{11})(\text{Q}_{12})$, $-\text{Si}(\text{Q}_{13})(\text{Q}_{14})(\text{Q}_{15})$, $-\text{Ge}(\text{Q}_{13})(\text{Q}_{14})(\text{Q}_{15})$, $-\text{B}(\text{Q}_{16})(\text{Q}_{17})$, $-\text{P}(\text{=O})(\text{Q}_{18})(\text{Q}_{19})$, $-\text{P}(\text{Q}_{18})(\text{Q}_{19})$, or any combination thereof;

a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_2\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group or a monovalent non-aromatic condensed heteropolycyclic group, each unsubstituted or substituted with deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, $-\text{CD}_3$, $-\text{CD}_2\text{H}$, $-\text{CDH}_2$, $-\text{CF}_3$, $-\text{CF}_2\text{H}$, $-\text{CFH}_2$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_1\text{-C}_{60}$ alkylthio group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_2\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-\text{N}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{Si}(\text{Q}_{23})(\text{Q}_{24})(\text{Q}_{25})$, $-\text{Ge}(\text{Q}_{23})(\text{Q}_{24})(\text{Q}_{25})$, $-\text{B}(\text{Q}_{26})(\text{Q}_{27})$, $-\text{P}(\text{=O})(\text{Q}_{28})(\text{Q}_{29})$, $-\text{P}(\text{Q}_{28})(\text{Q}_{29})$, or any combination thereof;

$-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{Si}(\text{Q}_{33})(\text{Q}_{34})(\text{Q}_{35})$, $-\text{Ge}(\text{Q}_{33})(\text{Q}_{34})(\text{Q}_{35})$, $-\text{B}(\text{Q}_{36})(\text{Q}_{37})$, $-\text{P}(\text{=O})(\text{Q}_{38})(\text{Q}_{39})$, or $-\text{P}(\text{Q}_{38})(\text{Q}_{39})$; or

any combination thereof,

wherein Q_1 to Q_9 , Q_{11} to Q_{19} , Q_{21} to Q_{29} , and Q_{31} to Q_{39} are each independently: hydrogen; deuterium; $-\text{F}$; $-\text{Cl}$; $-\text{Br}$; $-\text{I}$; a hydroxyl group; a cyano group; a nitro group; an amidino group; a hydrazine group; a hydrazone group; a carboxylic acid group or a salt thereof; a sulfonic acid group or a salt thereof; a phosphoric acid group or a salt thereof; a $\text{C}_1\text{-C}_{60}$ alkyl group which is unsubstituted or substituted with deuterium, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, or any combination thereof; a $\text{C}_2\text{-C}_{60}$ alkenyl group; a $\text{C}_2\text{-C}_{60}$ alkynyl group; a $\text{C}_1\text{-C}_{60}$ alkoxy group; a $\text{C}_1\text{-C}_{60}$ alkylthio group; a $\text{C}_3\text{-C}_{10}$ cycloalkyl group; a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group; a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group; a $\text{C}_2\text{-C}_{10}$ heterocycloalkenyl group; a $\text{C}_6\text{-C}_{60}$ aryl group which is unsubstituted or substituted with deuterium, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, or any combination thereof; a $\text{C}_6\text{-C}_{60}$ aryloxy group; a $\text{C}_6\text{-C}_{60}$ arylthio group; a $\text{C}_1\text{-C}_{60}$ heteroaryl group; a monovalent non-aromatic condensed polycyclic group; or a monovalent non-aromatic condensed heteropolycyclic group.

2. The organometallic compound of claim 1, wherein R_1 to R_8 , and A_7 in Formula 1 are each independently a group represented by Formula 2-1, a group represented by Formula 2-2, hydrogen, deuterium, $-\text{F}$, a substituted or unsubstituted $\text{C}_1\text{-C}_{20}$ alkyl group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a substituted or unsubstituted phenyl group, or a substituted or unsubstituted biphenyl group, and

Z_1 to Z_3 and Z_{11} to Z_{13} in Formula 2 are each independently hydrogen, deuterium, $-\text{F}$, a substituted or unsubstituted $\text{C}_1\text{-C}_{20}$ alkyl group, a substituted or

164

unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a substituted or unsubstituted phenyl group, or a substituted or unsubstituted biphenyl group.

3. The organometallic compound of claim 1, wherein R_1 to R_8 and A_7 in Formula 1 are each independently:

a group represented by Formula 2-1 or a group represented by Formula 2-2;

hydrogen, deuterium, or $-\text{F}$; or

a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a phenyl group, or a biphenyl group, each unsubstituted or substituted with deuterium, $-\text{F}$, $\text{C}_1\text{-C}_{20}$ alkyl group, a deuterated $\text{C}_1\text{-C}_{20}$ alkyl group, a fluorinated $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a deuterated $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a fluorinated $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $(\text{C}_1\text{-C}_{20})$ $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a deuterated $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a fluorinated $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $(\text{C}_1\text{-C}_{20})$ $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a phenyl group, a deuterated a phenyl group, a fluorinated a phenyl group, a $(\text{C}_1\text{-C}_{20})$ phenyl group, a biphenyl group, a deuterated a biphenyl group, a fluorinated a biphenyl group, a $(\text{C}_1\text{-C}_{20})$ biphenyl group, or any combination thereof,

R_9 and R_{11} in Formula A(1) are each independently:

a group represented by Formula 2-1 or a group represented by Formula 2-2; or

a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a phenyl group, or a biphenyl group, each unsubstituted or substituted with deuterium, a $\text{C}_1\text{-C}_{20}$ alkyl group, a deuterated $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a deuterated $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $(\text{C}_1\text{-C}_{20})$ $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a deuterated $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $(\text{C}_1\text{-C}_{20})$ $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a phenyl group, a deuterated a phenyl group, a $(\text{C}_1\text{-C}_{20})$ phenyl group, a biphenyl group, a deuterated a biphenyl group, a $(\text{C}_1\text{-C}_{20})$ biphenyl group, or any combination thereof, and

R_9 to R_{12} and R_{21} to R_{26} in Formulae A(2) to A(10) are each independently:

a group represented by Formula 2-1 or a group represented by Formula 2-2;

hydrogen, deuterium, or $-\text{F}$; or

a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a phenyl group, or a biphenyl group, each unsubstituted or substituted with deuterium, $-\text{F}$, a $\text{C}_1\text{-C}_{20}$ alkyl group, a deuterated $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a deuterated $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $(\text{C}_1\text{-C}_{20})$ $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a deuterated $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $(\text{C}_1\text{-C}_{20})$ $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a phenyl group, a deuterated a phenyl group, a $(\text{C}_1\text{-C}_{20})$ phenyl group, a biphenyl group, a deuterated a biphenyl group, a $(\text{C}_1\text{-C}_{20})$ biphenyl group, or any combination thereof.

4. The organometallic compound of claim 1, wherein at least one of R_3 to R_6 in Formula 1 is a group represented by Formula 2-2.

5. The organometallic compound of claim 1, wherein at least one of R_3 and R_5 in Formula 1 is independently a group represented by Formula 2-1 or a group represented by Formula 2-2.

165

6. The organometallic compound of claim 1, wherein, at least one of the R_3 to R_6 which is not the group represented by Formula 2-1 or Formula 2-2 is independently:

—F; or

a fluorinated C_1 - C_{20} alkyl group, a fluorinated C_3 - C_{10} cycloalkyl group, a fluorinated C_1 - C_{10} heterocycloalkyl group, a fluorinated phenyl group, or a fluorinated a biphenyl group, each unsubstituted or substituted with deuterium, —F, C_1 - C_{20} alkyl group, a deuterated C_1 - C_{20} alkyl group, a fluorinated C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, a deuterated C_3 - C_{10} cycloalkyl group, a fluorinated C_3 - C_{10} cycloalkyl group, a $(C_1$ - C_{20} alkyl) C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a deuterated C_1 - C_{10} heterocycloalkyl group, a fluorinated C_1 - C_{10} heterocycloalkyl group, a $(C_1$ - C_{20} alkyl) C_1 - C_{10} heterocycloalkyl group, a phenyl group, a deuterated a phenyl group, a fluorinated a phenyl group, a $(C_1$ - C_{20} alkyl)phenyl group, a biphenyl group, a deuterated a biphenyl group, a fluorinated a biphenyl group, a $(C_1$ - C_{20} alkyl) biphenyl group, or any combination thereof.

7. The organometallic compound of claim 1, wherein, at least one of R_3 to R_6 which is not the group represented by Formula 2-1 or Formula 2-2 is each independently:

deuterium; or

a deuterated C_1 - C_{20} alkyl group, a deuterated C_3 - C_{10} cycloalkyl group, a deuterated C_1 - C_{10} heterocycloalkyl group, a deuterated a phenyl group, or a deuterated a biphenyl group, each unsubstituted or substituted with deuterium, a C_1 - C_{20} alkyl group, a deuterated C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, a deuterated C_3 - C_{10} cycloalkyl group, a $(C_1$ - C_{20} alkyl) C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a deuterated C_1 - C_{10} heterocycloalkyl group, a $(C_1$ - C_{20} alkyl) C_1 - C_{10} heterocycloalkyl group, a phenyl group, a deuterated a phenyl group, a $(C_1$ - C_{20} alkyl) phenyl group, a biphenyl group, a deuterated a biphenyl group, a $(C_1$ - C_{20} alkyl) biphenyl group, or any combination thereof.

8. The organometallic compound of claim 1 wherein, at least one of R_3 to R_6 which is not the group represented by Formula 2-1 or Formula 2-2 is each independently:

hydrogen; or

a C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a phenyl group, or a biphenyl group, each unsubstituted or substituted with a C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, a $(C_1$ - C_{20} alkyl) C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a $(C_1$ - C_{20} alkyl) C_1 - C_{10} heterocycloalkyl group, a phenyl group, a $(C_1$ - C_{20} alkyl) phenyl group, a biphenyl group, a $(C_1$ - C_{20} alkyl) biphenyl group, or any combination thereof.

9. The organometallic compound of claim 1, wherein the organometallic compound satisfies at least one of Condition 1 to Condition 3:

Condition 1

A_1 to A_6 in Formula 1 are each independently a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_2 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

166

Condition 2

at least one of A_1 to A_6 in Formula 1 is a substituted or unsubstituted C_2 - C_{60} alkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_2 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and

Condition 3

A_7 in Formula 1 is deuterium, —F, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_2 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

10. The organometallic compound of claim 1, wherein the organometallic compound satisfies at least one of Condition 4 and Condition 5:


Condition 4

two or more of A_1 to A_3 in Formula 1 are linked together, and thus a group represented by $*-C(A_1)(A_2)(A_3)$ is a C_5 - C_{30} carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C_1 - C_{30} heterocyclic group unsubstituted or substituted with at least one R_{1a} , and


Condition 5

two or more of A_4 to A_6 in Formula 1 are linked together, and thus a group represented by $*-C(A_4)(A_5)(A_6)$ is a C_5 - C_{30} carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C_1 - C_{30} heterocyclic group unsubstituted or substituted with at least one R_{1a} .

11. The organometallic compound of claim 1, wherein a group represented by









in Formula 1 is a group represented by one of Formulae CY1 to CY24, CY41 to CY48 and CY57 to CY108



CY1

167

-continued

**168**

-continued

CY2

5

10

CY3 15

20

CY4 25

30

CY5 35

40

CY6 45







50

55

CY7

60

65



CY8

CY9

CY10








CY11

CY12

CY13

169


-continued

**170**

-continued

CY14


5



CY21

CY15


15



CY22

CY16


20



CY23

CY17


25



CY24

CY18


30



CY41

CY19


35



CY42

CY20

40









CY43







45

171

-continued

**172**

-continued



CY44

5

10

CY45

15

20

25

CY46

30

35

CY47

40

45

CY48

50

55

CY57

60

65

CY58

CY59

CY60


CY61

CY62

CY63

173


-continued



CY64

5


10



CY65 15


20

CY66 25




30

CY67 35



40


CY68 45



50

55

CY69




60


65

174


-continued




CY70




CY71




CY72



CY73




CY74



CY75

175


-continued



CY76


5

10



CY77 15


20



CY78 25


30

35




CY79 40

45



CY80 50

55




CY81 60


65

176


-continued




CY82




CY83




CY84



CY85









CY86



CY87

177


-continued

**178**

-continued


CY88

5




CY89

15




CY90

25




CY91

35




CY92

45



CY93

55



CY94

CY95






CY96

CY97

CY98

179


-continued

**180**

-continued

CY99


5



10

CY100

15




20

25

CY101


30



35

CY102


45



50

CY103

55



60

CY104

CY105

CY106

CY107

CY108

wherein, in Formulae CY1 to CY24, CY41 to CY48, and CY57 to CY108,

T₃ to T₆ are each independently a group represented by Formula 2-1 or a group represented by Formula 2-2,

65


181

R_2 to R_{22} and R_{1a} are the same as described in claim 1, and R_2 to R_8 are not hydrogen,

* is a binding site to Ir in Formula 1, and

*'' is a binding site to a neighboring atom in Formula 1. 5



12. The organometallic compound of claim 11, wherein a group represented by







in Formula 1 is a group represented by Formula CY9, CY11, CY12, CY14, or CY76.

13. The organometallic compound of claim 1, wherein R_9 and R_{11} in Formula A(1) are each independently: a C_1 - C_{20} alkyl group or a deuterated C_1 - C_{20} alkyl group.

14. The organometallic compound of claim 1, wherein the organometallic compound is at least one of Compounds 1 to 8, 10 and 12 to 16 below:

**182**


-continued



183

-continued

7




5

10

15

8


20



25

30


10 35



40

45

12 50



55


60

65


184

-continued


13




14



15



16



185

15. An organic light-emitting device comprising:

a first electrode;

a second electrode; and

an organic layer disposed between the first electrode and
the second electrode and comprising an emission layer, 5
wherein the organic layer comprises at least one organo-
metallic compound of claim 1.

16. The organic light-emitting device of claim **15**, wherein
the first electrode is an anode,

the second electrode is a cathode, 10

the organic layer further comprises a hole transport region
between the first electrode and the emission layer and
an electron transport region between the emission layer
and the second electrode,

the hole transport region comprises a hole injection layer, 15

a hole transport layer, an electron blocking layer, a
buffer layer, or any combination thereof, and

the electron transport region comprises a hole blocking
layer, an electron transport layer, an electron injection
layer, or any combination thereof. 20

17. The organic light-emitting device of claim **15**, wherein
the organometallic compound is included in the emission
layer.

18. An electronic apparatus comprising the organic light-
emitting device of claim **15**. 25

* * * * *

186