

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12385260
Kind Code	B2
Date of Patent	August 12, 2025
Inventor(s)	Cappelle; Mark

Floor covering, floor element and method for manufacturing floor elements

Abstract

A floor covering, made of floor elements, which, at least at two opposite sides, includes a male coupling part and a female coupling part, which allow that two of such floor elements to be interconnected by pushing one of these floor elements with the associated male coupling part, by a downward movement, home into the female coupling part of the other floor element. At least one of the coupling parts, either the male coupling part or the female coupling part, is made as least partially in a filled synthetic material composite, such as extruded wood.

Inventors:	Cappelle; Mark (Staden, BE)
Applicant:	UNILIN, BV (Wielsbeke, BE)
Family ID:	37649462
Assignee:	UNILIN, BV (Wielsbeke, BE)
Appl. No.:	18/435188
Filed:	February 07, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20240175271 A1	May. 30, 2024

Foreign Application Priority Data

BE	2006/0309	Jun. 02, 2006
----	-----------	---------------

Related U.S. Application Data

continuation parent-doc US 18169498 20230215 US 11933055 child-doc US 18435188
continuation parent-doc US 17195876 20210309 US 11680414 20230630 child-doc US 18169498

continuation parent-doc US 15930629 20200513 US 10975578 20210413 child-doc US 17195876
continuation parent-doc US 16670722 20191031 US 10745921 20200818 child-doc US 15930629
continuation parent-doc US 16510433 20190712 US 10519674 20191231 child-doc US 16670722
continuation parent-doc US 16160120 20181015 US 10358831 20190723 child-doc US 16510433
continuation parent-doc US 15866932 20180110 US 10125499 20181113 child-doc US 16160120
continuation parent-doc US 15623484 20170615 US 9890542 20180213 child-doc US 15866932
continuation parent-doc US 15342490 20161103 US 9695599 20170704 child-doc US 15623484
continuation parent-doc US 15151106 20160510 US 9487957 20161108 child-doc US 15342490
continuation parent-doc US 14672444 20150330 US 9366037 20160614 child-doc US 15151106
continuation parent-doc US 12303044 US 8991055 20150331 WO PCT/IB2007/000862 20070322
child-doc US 14672444

Publication Classification

Int. Cl.: E04F15/00 (20060101); E04F15/02 (20060101); E04F15/04 (20060101); E04F15/10 (20060101)

U.S. Cl.:

CPC E04F15/02038 (20130101); E04F15/02 (20130101); E04F15/02033 (20130101); E04F15/045 (20130101); E04F15/048 (20130101); E04F15/102 (20130101); E04F2201/0115 (20130101); E04F2201/013 (20130101); E04F2201/0138 (20130101); E04F2201/0146 (20130101); E04F2201/0153 (20130101); E04F2201/0161 (20130101); E04F2201/023 (20130101); E04F2201/026 (20130101); E04F2201/041 (20130101); E04F2201/043 (20130101); E04F2201/049 (20130101); E04F2201/0529 (20130101); Y10T29/49623 (20150115); Y10T29/49629 (20150115)

Field of Classification Search

CPC: E04F (15/02033); E04F (15/02038); E04F (15/107); E04F (15/102); E04F (2201/042); E04F (2201/0107); E04F (2201/03); E04F (2201/0552); E04F (2201/023); E04F (2201/0535); E04F (2201/0146); E04F (2201/043); E04F (2201/0547); E04F (2201/0153); E04F (2201/0138); E04F (15/02); E04F (2201/0115); E04F (2201/026); E04F (2201/011)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
124228	12/1871	Stuart	N/A	N/A
1194636	12/1915	Joy	N/A	N/A
1723306	12/1928	Sipe	N/A	N/A
1743492	12/1929	Sipe	N/A	N/A
1809393	12/1930	Rockwell	N/A	N/A
1902716	12/1932	Newton	N/A	N/A
1971067	12/1933	Fess	N/A	N/A
2026511	12/1934	Storm	N/A	N/A
2204675	12/1939	Grunert	N/A	N/A
2596280	12/1951	Nystrom	N/A	N/A

2732706	12/1955	Friedman	N/A	N/A
2740167	12/1955	Rowley	N/A	N/A
2863185	12/1957	Riedi	N/A	N/A
2865058	12/1957	Andersson et al.	N/A	N/A
3023681	12/1961	Worson	N/A	N/A
3077703	12/1962	Bergstrom	N/A	N/A
3173804	12/1964	Standfuss	N/A	N/A
3271787	12/1965	Clary	N/A	N/A
3325585	12/1966	Brenneman	N/A	N/A
3378958	12/1967	Parks et al.	N/A	N/A
3387422	12/1967	Wanzer	N/A	N/A
3396640	12/1967	Fujihara	N/A	N/A
3434861	12/1968	Luc	N/A	N/A
3512324	12/1969	Reed	N/A	N/A
3517927	12/1969	Kennel	N/A	N/A
3526071	12/1969	Watanabe	N/A	N/A
3535844	12/1969	Glaros	N/A	N/A
3554827	12/1970	Yamagishi	N/A	N/A
3572224	12/1970	Perry	N/A	N/A
3579941	12/1970	Tibbals	N/A	N/A
3720027	12/1972	Christensen	N/A	N/A
3731445	12/1972	Hoffmann et al.	N/A	N/A
3741851	12/1972	Erb et al.	N/A	N/A
3742669	12/1972	Mansfeld	N/A	N/A
3760547	12/1972	Brenneman	N/A	N/A
3778954	12/1972	Meserole	N/A	N/A
3786608	12/1973	Boettcher	N/A	N/A
3810774	12/1973	Pittman	N/A	N/A
3811915	12/1973	Burrell et al.	N/A	N/A
3849235	12/1973	Gwynne	N/A	N/A
3853685	12/1973	Friedrich et al.	N/A	N/A
3905849	12/1974	Bomboire	N/A	N/A
3919820	12/1974	Green	N/A	N/A
3950915	12/1975	Cole	N/A	N/A
3980173	12/1975	Riggs	N/A	N/A
4030852	12/1976	Hein	N/A	N/A
4050409	12/1976	Duchenaud et al.	N/A	N/A
4064571	12/1976	Phipps	N/A	N/A
4080086	12/1977	Watson	N/A	N/A
4082129	12/1977	Morelock	N/A	N/A
4097635	12/1977	Sanz Hernandez et al.	N/A	N/A
4100710	12/1977	Kowallik	N/A	N/A
4107892	12/1977	Bellem	N/A	N/A
4113399	12/1977	Hansen, Sr.	N/A	N/A
4169688	12/1978	Toshio	N/A	N/A
4196554	12/1979	Anderson et al.	N/A	N/A
4225374	12/1979	Kaufmann	N/A	N/A
4227430	12/1979	Jansson et al.	N/A	N/A
4233343	12/1979	Barker et al.	N/A	N/A

4299070	12/1980	Oltmanns et al.	N/A	N/A
4304083	12/1980	Anderson	N/A	N/A
4312686	12/1981	Smith et al.	N/A	N/A
4379198	12/1982	Jaeschke et al.	N/A	N/A
4396566	12/1982	Brinkmann et al.	N/A	N/A
4397896	12/1982	Moran	N/A	N/A
4400862	12/1982	Ignell	N/A	N/A
4426820	12/1983	Terbrack et al.	N/A	N/A
4512131	12/1984	Laramore	N/A	N/A
4599841	12/1985	Haid	N/A	N/A
4614680	12/1985	Fry et al.	N/A	N/A
4648165	12/1986	Whitehorne	N/A	N/A
4690434	12/1986	Schmidt	N/A	N/A
4724187	12/1987	Ungar et al.	N/A	N/A
4819932	12/1988	Trotter, Jr.	N/A	N/A
4948653	12/1989	Dinter et al.	N/A	N/A
5007222	12/1990	Raymond	N/A	N/A
5071282	12/1990	Brown	N/A	N/A
5077112	12/1990	Hensel et al.	N/A	N/A
5082495	12/1991	Iijima	N/A	N/A
5109898	12/1991	Schacht	N/A	N/A
5112671	12/1991	Diamond et al.	N/A	N/A
5135597	12/1991	Barker	N/A	N/A
5148850	12/1991	Urbanick	N/A	N/A
5173012	12/1991	Ortwein et al.	N/A	N/A
5182892	12/1992	Chase	N/A	N/A
5247773	12/1992	Weir	N/A	N/A
5261508	12/1992	Kikuchi	N/A	N/A
5295341	12/1993	Kajiwara	N/A	N/A
5344700	12/1993	Mcgath et al.	N/A	N/A
5348778	12/1993	Knipp et al.	N/A	N/A
5437934	12/1994	Witt et al.	N/A	N/A
5465546	12/1994	Buse	N/A	N/A
5506031	12/1995	Spain et al.	N/A	N/A
5516472	12/1995	Laver	N/A	N/A
5548937	12/1995	Shimonohara	N/A	N/A
5560797	12/1995	Burt et al.	N/A	N/A
5598682	12/1996	Haughian	N/A	N/A
5618602	12/1996	Nelson	N/A	N/A
5634309	12/1996	Polen	N/A	N/A
5694730	12/1996	Del Rincon et al.	N/A	N/A
5706621	12/1997	Pervan	N/A	N/A
5755068	12/1997	Ormiston	N/A	N/A
5836128	12/1997	Groh et al.	N/A	N/A
5860267	12/1998	Pervan	N/A	N/A
5863632	12/1998	Bisker	N/A	N/A
5899038	12/1998	Stroppiana	N/A	N/A
5916662	12/1998	Schmidt	N/A	N/A
5950389	12/1998	Porter	N/A	N/A
5952076	12/1998	Foster	N/A	N/A

5988503	12/1998	Kuo	N/A	N/A
6006486	12/1998	Moriau et al.	N/A	N/A
6023907	12/1999	Pervan	N/A	N/A
6052960	12/1999	Yonemura	N/A	N/A
6065262	12/1999	Motta	N/A	N/A
6173548	12/2000	Hamar et al.	N/A	N/A
6182410	12/2000	Pervan	N/A	N/A
6203653	12/2000	Seidner	N/A	N/A
6216409	12/2000	Roy et al.	N/A	N/A
6254301	12/2000	Hatch	N/A	N/A
6256959	12/2000	Palmersten	N/A	N/A
6272437	12/2000	Woods et al.	N/A	N/A
6295779	12/2000	Canfield	N/A	N/A
6296732	12/2000	Enlow et al.	N/A	N/A
6306318	12/2000	Ricciardelli et al.	N/A	N/A
6314701	12/2000	Meyerson	N/A	N/A
6324803	12/2000	Pervan	N/A	N/A
6333094	12/2000	Schneider et al.	N/A	N/A
6345481	12/2001	Nelson	N/A	N/A
6358352	12/2001	Schmidt	N/A	N/A
6363677	12/2001	Chen et al.	N/A	N/A
6385936	12/2001	Schneider	N/A	N/A
6418683	12/2001	Martensson et al.	N/A	N/A
6428871	12/2001	Cozzolino	N/A	N/A
6444075	12/2001	Schneider et al.	N/A	N/A
6446413	12/2001	Gruber	N/A	N/A
6450235	12/2001	Lee	N/A	N/A
6465046	12/2001	Hansson et al.	N/A	N/A
6477948	12/2001	Nissing et al.	N/A	N/A
6490836	12/2001	Moriau et al.	N/A	N/A
6505452	12/2002	Hannig et al.	N/A	N/A
6516579	12/2002	Pervan	N/A	N/A
6536178	12/2002	Palsson et al.	N/A	N/A
6550206	12/2002	Lee	N/A	N/A
6553724	12/2002	Bigler	N/A	N/A
6576079	12/2002	Kai	N/A	N/A
6591568	12/2002	Palsson	N/A	N/A
6601359	12/2002	Olofsson	N/A	N/A
6617009	12/2002	Chen et al.	N/A	N/A
6647689	12/2002	Pletzer et al.	N/A	N/A
6647690	12/2002	Martensson	N/A	N/A
6651400	12/2002	Murphy	N/A	N/A
6681820	12/2003	Olofsson	N/A	N/A
6729091	12/2003	Martensson	N/A	N/A
6763643	12/2003	Martensson	N/A	N/A
6769219	12/2003	Schwitte et al.	N/A	N/A
6772568	12/2003	Thiers et al.	N/A	N/A
6802166	12/2003	Gerhard	N/A	N/A
6804926	12/2003	Eisermann	N/A	N/A
6854235	12/2004	Martensson	N/A	N/A

6862857	12/2004	Tychsen	N/A	N/A
6865855	12/2004	Knauseder	N/A	N/A
6874291	12/2004	Weber	N/A	N/A
6874292	12/2004	Moriau et al.	N/A	N/A
6880307	12/2004	Schwitte et al.	N/A	N/A
6928779	12/2004	Moriau et al.	N/A	N/A
6931811	12/2004	Thiers	N/A	N/A
6933043	12/2004	Son et al.	N/A	N/A
6955020	12/2004	Moriau et al.	N/A	N/A
6979487	12/2004	Scarborough et al.	N/A	N/A
6986934	12/2005	Chen et al.	N/A	N/A
6991830	12/2005	Hansson et al.	N/A	N/A
6993877	12/2005	Moriau et al.	N/A	N/A
7021019	12/2005	Kanuseder	N/A	N/A
7040068	12/2005	Moriau et al.	N/A	N/A
7051486	12/2005	Pervan	N/A	N/A
7149633	12/2005	Woods et al.	N/A	N/A
7152383	12/2005	Wilkinson, Jr. et al.	N/A	N/A
7169460	12/2006	Chen et al.	N/A	N/A
7188456	12/2006	Knauseder	N/A	N/A
7211310	12/2006	Chen et al.	N/A	N/A
7219392	12/2006	Mullet et al.	N/A	N/A
7243469	12/2006	Miller et al.	N/A	N/A
7251916	12/2006	Konzelmann et al.	N/A	N/A
7261947	12/2006	Reichwein et al.	N/A	N/A
7328536	12/2007	Moriau et al.	N/A	N/A
7337588	12/2007	Moebus	N/A	N/A
7343717	12/2007	Thiers et al.	N/A	N/A
7377081	12/2007	Ruhdorfer	N/A	N/A
7419717	12/2007	Chen et al.	N/A	N/A
7451578	12/2007	Hannig	N/A	N/A
7454875	12/2007	Pervan et al.	N/A	N/A
7467499	12/2007	Moriau et al.	N/A	N/A
7516588	12/2008	Pervan	N/A	N/A
7533500	12/2008	Morton et al.	N/A	N/A
7544423	12/2008	Horton	N/A	N/A
7552568	12/2008	Palsson et al.	N/A	N/A
7556849	12/2008	Thompson et al.	N/A	N/A
7568322	12/2008	Pervan	N/A	N/A
7584583	12/2008	Bergelin et al.	N/A	N/A
7596920	12/2008	Konstanczak	N/A	N/A
7603826	12/2008	Moebus	N/A	N/A
7614197	12/2008	Nelson	N/A	N/A
7617645	12/2008	Moriau et al.	N/A	N/A
7617651	12/2008	Grafenauer	N/A	N/A
7621092	12/2008	Groeke et al.	N/A	N/A
7621094	12/2008	Moriau et al.	N/A	N/A
7634886	12/2008	Moriau et al.	N/A	N/A
7634887	12/2008	Moriau et al.	N/A	N/A

7634884	12/2008	Pervan et al.	N/A	N/A
7637066	12/2008	Moriau et al.	N/A	N/A
7637067	12/2008	Moriau et al.	N/A	N/A
7637068	12/2008	Pervan	N/A	N/A
7640708	12/2009	Moriau et al.	N/A	N/A
7644554	12/2009	Moriau et al.	N/A	N/A
7644555	12/2009	Moriau et al.	N/A	N/A
7644557	12/2009	Moriau et al.	N/A	N/A
7647741	12/2009	Moriau et al.	N/A	N/A
7647743	12/2009	Moriau et al.	N/A	N/A
7650727	12/2009	Moriau et al.	N/A	N/A
7650728	12/2009	Moriau et al.	N/A	N/A
7654054	12/2009	Moriau et al.	N/A	N/A
7658048	12/2009	Moriau et al.	N/A	N/A
7661238	12/2009	Moriau et al.	N/A	N/A
7665265	12/2009	Moriau et al.	N/A	N/A
7665266	12/2009	Moriau et al.	N/A	N/A
7665267	12/2009	Moriau et al.	N/A	N/A
7665268	12/2009	Moriau et al.	N/A	N/A
7669376	12/2009	Moriau et al.	N/A	N/A
7669377	12/2009	Moriau et al.	N/A	N/A
7673431	12/2009	Moriau et al.	N/A	N/A
7677005	12/2009	Pervan	N/A	N/A
7677008	12/2009	Moriau et al.	N/A	N/A
7681371	12/2009	Moriau et al.	N/A	N/A
7698868	12/2009	Moriau et al.	N/A	N/A
7698869	12/2009	Moriau et al.	N/A	N/A
7707793	12/2009	Moriau et al.	N/A	N/A
7712280	12/2009	Moriau et al.	N/A	N/A
7721503	12/2009	Pervan et al.	N/A	N/A
7726089	12/2009	Moriau et al.	N/A	N/A
7735288	12/2009	Moriau et al.	N/A	N/A
7757452	12/2009	Pervan	N/A	N/A
7757453	12/2009	Moriau et al.	N/A	N/A
7762035	12/2009	Cappelle	N/A	N/A
7763345	12/2009	Chen et al.	N/A	N/A
7770350	12/2009	Moriau et al.	N/A	N/A
7779597	12/2009	Thiers et al.	N/A	N/A
7802415	12/2009	Pervan et al.	N/A	N/A
7806624	12/2009	McClean et al.	N/A	N/A
7810297	12/2009	Moriau et al.	N/A	N/A
7827754	12/2009	Moriau et al.	N/A	N/A
7827755	12/2009	Moriau et al.	N/A	N/A
7841145	12/2009	Pervan et al.	N/A	N/A
7856785	12/2009	Pervan	N/A	N/A
7866115	12/2010	Pervan et al.	N/A	N/A
7877956	12/2010	Martensson	N/A	N/A
7896571	12/2010	Hannig et al.	N/A	N/A
7918062	12/2010	Chen	N/A	N/A
7980043	12/2010	Moebus	N/A	N/A

8021741	12/2010	Chen et al.	N/A	N/A
8024904	12/2010	Hannig	N/A	N/A
8099919	12/2011	Garcia	N/A	N/A
8153234	12/2011	Nollet et al.	N/A	N/A
8156705	12/2011	Alford et al.	N/A	N/A
8161701	12/2011	Cappelle et al.	N/A	N/A
8166723	12/2011	Moriau et al.	N/A	N/A
8176698	12/2011	Lewark	N/A	N/A
8182928	12/2011	Horton	N/A	N/A
8191334	12/2011	Braun	N/A	N/A
8245477	12/2011	Pervan	N/A	N/A
8272187	12/2011	Meersseman et al.	N/A	N/A
8293058	12/2011	Pervan et al.	N/A	N/A
8365494	12/2012	Moriau et al.	N/A	N/A
8375672	12/2012	Hannig	N/A	N/A
8438814	12/2012	Thiers et al.	N/A	N/A
8596013	12/2012	Boo	N/A	N/A
8615953	12/2012	Cappelle	N/A	N/A
8621814	12/2013	Cappelle	N/A	N/A
8631625	12/2013	Thiers et al.	N/A	N/A
8689512	12/2013	Pervan	N/A	N/A
8726603	12/2013	Huang	N/A	N/A
8789334	12/2013	Moriau et al.	N/A	N/A
8793958	12/2013	Thiers et al.	N/A	N/A
8839584	12/2013	Sokol	N/A	N/A
8904729	12/2013	Thiers et al.	N/A	N/A
8991055	12/2014	Cappelle	N/A	N/A
8997429	12/2014	Moriau et al.	N/A	N/A
9140010	12/2014	Pervan	N/A	N/A
9145691	12/2014	Cappelle	N/A	N/A
9200460	12/2014	Cappelle	N/A	N/A
9216541	12/2014	Boo et al.	N/A	N/A
9290948	12/2015	Cappelle et al.	N/A	N/A
9290951	12/2015	Moriau et al.	N/A	N/A
9314888	12/2015	Pervan et al.	N/A	N/A
9316002	12/2015	Boo	N/A	N/A
9322183	12/2015	Pervan	N/A	N/A
9366037	12/2015	Cappelle	N/A	N/A
9487957	12/2015	Cappelle	N/A	N/A
9695599	12/2016	Cappelle	N/A	N/A
9890542	12/2017	Cappelle	N/A	N/A
10125499	12/2017	Cappelle	N/A	N/A
10358831	12/2018	Cappelle	N/A	N/A
10519674	12/2018	Cappelle	N/A	N/A
10745921	12/2019	Cappelle	N/A	N/A
10975578	12/2020	Cappelle	N/A	N/A
10975579	12/2020	Cappelle	N/A	N/A
11680414	12/2022	Cappelle	N/A	N/A
11933055	12/2023	Cappelle	N/A	E04F 15/048

12110693	12/2023	Devos	N/A	E04F 15/02038
2001/0034991	12/2000	Martensson et al.	N/A	N/A
2002/0020127	12/2001	Thiers et al.	N/A	N/A
2002/0025446	12/2001	Chen et al.	N/A	N/A
2002/0031646	12/2001	Chen et al.	N/A	N/A
2002/0046527	12/2001	Nelson	N/A	N/A
2002/0092263	12/2001	Schulte	N/A	N/A
2002/0136862	12/2001	Dong et al.	N/A	N/A
2002/0142106	12/2001	Bethune et al.	N/A	N/A
2002/0170259	12/2001	Ferris	N/A	N/A
2002/0178674	12/2001	Pervan	N/A	N/A
2002/0178680	12/2001	Martensson et al.	N/A	N/A
2002/0189183	12/2001	Ricciardelli	N/A	N/A
2003/0009971	12/2002	Palmberg	N/A	N/A
2003/0024199	12/2002	Pervan et al.	N/A	N/A
2003/0029116	12/2002	Moriau et al.	N/A	N/A
2003/0029117	12/2002	Moriau et al.	N/A	N/A
2003/0033777	12/2002	Thiers et al.	N/A	N/A
2003/0037504	12/2002	Schwitte et al.	N/A	N/A
2003/0097808	12/2002	Sabatini	N/A	N/A
2003/0101681	12/2002	Tychsen	N/A	N/A
2003/0136494	12/2002	Windmoller et al.	N/A	N/A
2003/0145549	12/2002	Palsson et al.	N/A	N/A
2003/0159385	12/2002	Thiers	N/A	N/A
2003/0180091	12/2002	Stridsman	N/A	N/A
2003/0188504	12/2002	Ralf	N/A	N/A
2003/0196405	12/2002	Pervan	N/A	N/A
2003/0224147	12/2002	Maine et al.	N/A	N/A
2003/0233809	12/2002	Pervan	N/A	N/A
2003/0236642	12/2002	Timans	N/A	N/A
2004/0016196	12/2003	Pervan	N/A	N/A
2004/0016197	12/2003	Ruhdorfer	N/A	N/A
2004/0026017	12/2003	Taylor et al.	N/A	N/A
2004/0031227	12/2003	Knauseder	N/A	N/A
2004/0049999	12/2003	Krieger	N/A	N/A
2004/0060255	12/2003	Knauseder	N/A	N/A
2004/0068954	12/2003	Martensson	N/A	N/A
2004/0071978	12/2003	Hallenbeck et al.	N/A	N/A
2004/0102120	12/2003	Plusquellec et al.	N/A	N/A
2004/0107659	12/2003	Glockl	N/A	N/A
2004/0123548	12/2003	Gimpel et al.	N/A	N/A
2004/0128934	12/2003	Hecht	N/A	N/A
2004/0137248	12/2003	Elsasser	N/A	N/A
2004/0139678	12/2003	Pervan	N/A	N/A
2004/0146695	12/2003	Hardwick	N/A	N/A
2004/0161588	12/2003	Mauk et al.	N/A	N/A
2004/0182036	12/2003	Sjoberg et al.	N/A	N/A
2004/0191547	12/2003	Oldorff	N/A	N/A
2004/0200175	12/2003	Weber	N/A	N/A

2004/0211143	12/2003	Hanning	N/A	N/A
2004/0211144	12/2003	Stanchfield	N/A	N/A
2004/0248489	12/2003	Hutchison et al.	N/A	N/A
2004/0250493	12/2003	Thiers et al.	N/A	N/A
2004/0255538	12/2003	Ruhdorfer	N/A	N/A
2004/0261348	12/2003	Vulin	N/A	N/A
2005/0003160	12/2004	Chen et al.	N/A	N/A
2005/0025934	12/2004	Thiers	N/A	N/A
2005/0050827	12/2004	Schitter	N/A	N/A
2005/0076598	12/2004	Lewark	N/A	N/A
2005/0144881	12/2004	Tate et al.	N/A	N/A
2005/0153243	12/2004	Rundle et al.	N/A	N/A
2005/0160694	12/2004	Pervan	N/A	N/A
2005/0166514	12/2004	Pervan	N/A	N/A
2005/0166515	12/2004	Boucke	N/A	N/A
2005/0192382	12/2004	Maine et al.	N/A	N/A
2005/0210810	12/2004	Pervan	N/A	N/A
2005/0221056	12/2004	Schwonke et al.	N/A	N/A
2005/0235593	12/2004	Hecht	N/A	N/A
2005/0252130	12/2004	Martensson	N/A	N/A
2005/0281986	12/2004	Nam	N/A	N/A
2005/0284075	12/2004	Moriau et al.	N/A	N/A
2005/0284076	12/2004	Moriau et al.	N/A	N/A
2006/0005499	12/2005	Moriau et al.	N/A	N/A
2006/0008630	12/2005	Thiers et al.	N/A	N/A
2006/0032175	12/2005	Chen et al.	N/A	N/A
2006/0032177	12/2005	Moriau et al.	N/A	N/A
2006/0070332	12/2005	Palsson et al.	N/A	N/A
2006/0070333	12/2005	Pervan	N/A	N/A
2006/0101769	12/2005	Pervan et al.	N/A	N/A
2006/0105145	12/2005	Brown	N/A	N/A
2006/0179773	12/2005	Pervan	N/A	N/A
2006/0186233	12/2005	Holm et al.	N/A	N/A
2006/0196138	12/2005	Moriau et al.	N/A	N/A
2006/0201095	12/2005	Moriau et al.	N/A	N/A
2006/0204773	12/2005	Kwon et al.	N/A	N/A
2006/0225370	12/2005	Moriau et al.	N/A	N/A
2006/0225377	12/2005	Moriau et al.	N/A	N/A
2006/0236630	12/2005	Moriau et al.	N/A	N/A
2006/0236631	12/2005	Moriau et al.	N/A	N/A
2006/0236632	12/2005	Moriau et al.	N/A	N/A
2006/0236633	12/2005	Moriau et al.	N/A	N/A
2006/0236634	12/2005	Moriau et al.	N/A	N/A
2006/0236635	12/2005	Moriau et al.	N/A	N/A
2006/0236636	12/2005	Moriau et al.	N/A	N/A
2006/0236637	12/2005	Moriau et al.	N/A	N/A
2006/0236638	12/2005	Moriau et al.	N/A	N/A
2006/0236642	12/2005	Pervan	N/A	N/A
2006/0236643	12/2005	Moriau et al.	N/A	N/A
2006/0248829	12/2005	Moriau et al.	N/A	N/A

2006/0248830	12/2005	Moriau et al.	N/A	N/A
2006/0248831	12/2005	Moriau et al.	N/A	N/A
2006/0254183	12/2005	Moriau et al.	N/A	N/A
2006/0254184	12/2005	Moriau et al.	N/A	N/A
2006/0254185	12/2005	Moriau et al.	N/A	N/A
2006/0260249	12/2005	Moriau et al.	N/A	N/A
2006/0260252	12/2005	Brice	N/A	N/A
2006/0260253	12/2005	Brice	N/A	N/A
2006/0260254	12/2005	Pervan	N/A	N/A
2006/0272263	12/2005	Moriau et al.	N/A	N/A
2006/0280870	12/2005	Halot et al.	N/A	N/A
2007/0006543	12/2006	Engstrom	N/A	N/A
2007/0022694	12/2006	Chen et al.	N/A	N/A
2007/0028547	12/2006	Grafenauer et al.	N/A	N/A
2007/0039664	12/2006	Quick	N/A	N/A
2007/0051064	12/2006	Thiers	N/A	N/A
2007/0094978	12/2006	Svanholm et al.	N/A	N/A
2007/0094986	12/2006	Moriau et al.	N/A	N/A
2007/0094987	12/2006	Moriau et al.	N/A	N/A
2007/0107360	12/2006	Moriau et al.	N/A	N/A
2007/0107363	12/2006	Moriau et al.	N/A	N/A
2007/0130872	12/2006	Goodwin et al.	N/A	N/A
2007/0151189	12/2006	Yang	N/A	N/A
2007/0175156	12/2006	Pervan et al.	N/A	N/A
2007/0175160	12/2006	Groeke et al.	N/A	N/A
2007/0193178	12/2006	Groeke et al.	N/A	N/A
2007/0251188	12/2006	Moriau et al.	N/A	N/A
2008/0000186	12/2007	Pervan et al.	N/A	N/A
2008/0005999	12/2007	Pervan	N/A	N/A
2008/0010928	12/2007	Moriau et al.	N/A	N/A
2008/0010929	12/2007	Moriau et al.	N/A	N/A
2008/0010931	12/2007	Pervan et al.	N/A	N/A
2008/0010937	12/2007	Pervan et al.	N/A	N/A
2008/0028707	12/2007	Pervan	N/A	N/A
2008/0029926	12/2007	Steinwender et al.	N/A	N/A
2008/0034701	12/2007	Pervan	N/A	N/A
2008/0034708	12/2007	Pervan	N/A	N/A
2008/0041008	12/2007	Pervan	N/A	N/A
2008/0053027	12/2007	Moriau et al.	N/A	N/A
2008/0053028	12/2007	Moriau et al.	N/A	N/A
2008/0060308	12/2007	Pervan	N/A	N/A
2008/0060309	12/2007	Moriau et al.	N/A	N/A
2008/0060310	12/2007	Moriau et al.	N/A	N/A
2008/0060311	12/2007	Moriau et al.	N/A	N/A
2008/0066415	12/2007	Pervan et al.	N/A	N/A
2008/0066416	12/2007	Moriau et al.	N/A	N/A
2008/0104921	12/2007	Pervan et al.	N/A	N/A
2008/0110125	12/2007	Pervan	N/A	N/A
2008/0134607	12/2007	Pervan et al.	N/A	N/A
2008/0134613	12/2007	Pervan	N/A	N/A

2008/0134614	12/2007	Pervan et al.	N/A	N/A
2008/0138560	12/2007	Windmoller	N/A	N/A
2008/0168736	12/2007	Pervan	N/A	N/A
2008/0168737	12/2007	Pervan	N/A	N/A
2008/0172856	12/2007	Brouckaert et al.	N/A	N/A
2008/0216920	12/2007	Pervan	N/A	N/A
2008/0261019	12/2007	Shen et al.	N/A	N/A
2008/0295432	12/2007	Pervan et al.	N/A	N/A
2008/0301945	12/2007	Gibson et al.	N/A	N/A
2008/0305312	12/2007	Kim et al.	N/A	N/A
2008/0311355	12/2007	Chen et al.	N/A	N/A
2009/0019801	12/2008	Coghlan et al.	N/A	N/A
2009/0031662	12/2008	Chen et al.	N/A	N/A
2009/0078129	12/2008	Cappelle et al.	N/A	N/A
2009/0151291	12/2008	Pervan	N/A	N/A
2009/0193748	12/2008	Boo et al.	N/A	N/A
2009/0249733	12/2008	Moebus	N/A	N/A
2009/0260307	12/2008	Thiers	N/A	N/A
2009/0260313	12/2008	Segaert	N/A	N/A
2010/0043333	12/2009	Hannig	N/A	N/A
2010/0170189	12/2009	Schulte	N/A	N/A
2010/0300031	12/2009	Pervan et al.	N/A	N/A
2010/0319290	12/2009	Pervan et al.	N/A	N/A
2010/0319291	12/2009	Pervan et al.	N/A	N/A
2010/0319292	12/2009	Moriau et al.	N/A	N/A
2011/0023405	12/2010	Moriau et al.	N/A	N/A
2011/0030303	12/2010	Pervan et al.	N/A	N/A
2011/0088344	12/2010	Pervan et al.	N/A	N/A
2011/0088345	12/2010	Pervan et al.	N/A	N/A
2011/0154665	12/2010	Pervan et al.	N/A	N/A
2011/0167750	12/2010	Pervan	N/A	N/A
2011/0225922	12/2010	Pervan et al.	N/A	N/A
2011/0252733	12/2010	Pervan et al.	N/A	N/A
2011/0283650	12/2010	Pervan et al.	N/A	N/A
2012/0017533	12/2011	Pervan et al.	N/A	N/A
2012/0031029	12/2011	Pervan et al.	N/A	N/A
2012/0036804	12/2011	Pervan	N/A	N/A
2012/0151865	12/2011	Pervan et al.	N/A	N/A
2012/0174515	12/2011	Pervan et al.	N/A	N/A
2013/0042562	12/2012	Pervan et al.	N/A	N/A
2013/0104487	12/2012	Moriau et al.	N/A	N/A
2014/0033635	12/2013	Pervan et al.	N/A	N/A
2014/0033636	12/2013	Cappelle	N/A	N/A
2014/0290174	12/2013	Moriau et al.	N/A	N/A
2015/0204080	12/2014	Cappelle	N/A	N/A
2015/0204081	12/2014	Cappelle	N/A	N/A
2015/0211238	12/2014	Moriau et al.	N/A	N/A
2016/0251861	12/2015	Cappelle	N/A	N/A
2017/0051514	12/2016	Cappelle	N/A	N/A
2017/0284106	12/2016	Cappelle	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
1017157	12/2007	BE	N/A
991 373	12/1975	CA	N/A
2 359 419	12/2001	CA	N/A
2 456 513	12/2002	CA	N/A
1119152	12/1995	CN	N/A
1122623	12/1995	CN	N/A
1195386	12/1997	CN	N/A
2301491	12/1997	CN	N/A
2364121	12/1999	CN	N/A
1482166	12/2003	CN	N/A
2765969	12/2005	CN	N/A
1911997	12/2006	CN	N/A
101023230	12/2006	CN	N/A
101072691	12/2006	CN	N/A
100354492	12/2006	CN	N/A
100523404	12/2008	CN	N/A
138385	12/1900	DE	N/A
1 534 802	12/1969	DE	N/A
2 159 042	12/1972	DE	N/A
27 21 292	12/1977	DE	N/A
28 56 391	12/1979	DE	N/A
2940945	12/1980	DE	N/A
33 43 601	12/1984	DE	N/A
254 920	12/1987	DE	N/A
39 32 980	12/1990	DE	N/A
42 15 273	12/1992	DE	N/A
42 42 530	12/1993	DE	N/A
195 32 819	12/1996	DE	N/A
196 01 322	12/1996	DE	N/A
197 25 829	12/1997	DE	N/A
200 08 708	12/1999	DE	N/A
199 40 837	12/1999	DE	N/A
19944399	12/2000	DE	N/A
199 58 225	12/2000	DE	N/A
200 20 505	12/2001	DE	N/A
202 05 774	12/2001	DE	N/A
101 38 285	12/2002	DE	N/A
203 00 306	12/2002	DE	N/A
202 03 782	12/2002	DE	N/A
203 10 959	12/2002	DE	N/A
203 00 291	12/2002	DE	N/A
103 05 695	12/2003	DE	N/A
103 16 695	12/2003	DE	N/A
20 2004 018 661	12/2004	DE	N/A
203 20 799	12/2004	DE	N/A

10 2004 055 951	12/2004	DE	N/A
10 2004 001 363	12/2004	DE	N/A
10 2005 002 297	12/2004	DE	N/A
10 2004 009 160	12/2004	DE	N/A
10 2004 012 582	12/2004	DE	N/A
10 2004 023 157	12/2004	DE	N/A
20 2005 019 427	12/2005	DE	N/A
10 2006 054 023	12/2006	DE	N/A
0 007 230	12/1979	EP	N/A
0 013 852	12/1979	EP	N/A
0 130 559	12/1984	EP	N/A
0 562 402	12/1992	EP	N/A
0 864 712	12/1997	EP	N/A
0893473	12/1998	EP	N/A
0 974 713	12/1999	EP	N/A
1 026 341	12/1999	EP	N/A
1 120 515	12/2000	EP	N/A
1 138 467	12/2000	EP	N/A
1 146 182	12/2000	EP	N/A
1 154 090	12/2000	EP	N/A
1 247 641	12/2001	EP	N/A
1 262 607	12/2001	EP	N/A
1 262 609	12/2001	EP	N/A
1 279 778	12/2002	EP	N/A
1 290 290	12/2002	EP	N/A
1 308 577	12/2002	EP	N/A
1 033 201	12/2002	EP	N/A
1 350 904	12/2002	EP	N/A
1382774	12/2003	EP	N/A
1 420 125	12/2003	EP	N/A
1 441 086	12/2003	EP	N/A
1 454 763	12/2003	EP	N/A
1 469 140	12/2003	EP	N/A
1 493 879	12/2004	EP	N/A
1 593 795	12/2004	EP	N/A
1 593 796	12/2004	EP	N/A
1 650 375	12/2005	EP	N/A
1 705 309	12/2005	EP	N/A
1 872 959	12/2007	EP	N/A
1 892 352	12/2007	EP	N/A
1 938 963	12/2007	EP	N/A
2843155	12/2014	EP	N/A
2843155	12/2016	EP	N/A
1 138 595	12/1956	FR	N/A
2 149 112	12/1972	FR	N/A
2 256 807	12/1974	FR	N/A
2 271 365	12/1974	FR	N/A
2 609 664	12/1987	FR	N/A
2 810 060	12/2000	FR	N/A
2 827 529	12/2002	FR	N/A

240 629	12/1924	GB	N/A
518 239	12/1939	GB	N/A
900 958	12/1961	GB	N/A
1 015 701	12/1965	GB	N/A
1 171 337	12/1968	GB	N/A
1 467 899	12/1976	GB	N/A
1 520 964	12/1977	GB	N/A
2 020 998	12/1978	GB	N/A
2 051 916	12/1980	GB	N/A
2 145 371	12/1984	GB	N/A
2 376 916	12/2001	GB	N/A
S60-255843	12/1984	JP	N/A
S62-127225	12/1986	JP	N/A
H03-110258	12/1990	JP	N/A
H03-169967	12/1990	JP	N/A
H05-18028	12/1992	JP	N/A
H05-131594	12/1992	JP	N/A
H05-214803	12/1992	JP	N/A
H06-64108	12/1993	JP	N/A
H06-146553	12/1993	JP	N/A
H06-288017	12/1993	JP	N/A
H06-306961	12/1993	JP	N/A
H06-322848	12/1993	JP	N/A
H07-180333	12/1994	JP	N/A
2000-170361	12/1999	JP	N/A
950019071	12/1994	KR	N/A
960005785	12/1995	KR	N/A
2001048980000	12/1996	KR	N/A
20-0399316	12/2004	KR	N/A
8000083	12/1980	NL	N/A
94/26999	12/1993	WO	N/A
95/11333	12/1994	WO	N/A
96/27721	12/1995	WO	N/A
97/18949	12/1996	WO	N/A
97/47834	12/1996	WO	N/A
99/17930	12/1998	WO	N/A
99/45060	12/1998	WO	N/A
99/66151	12/1998	WO	N/A
99/66152	12/1998	WO	N/A
00/20705	12/1999	WO	N/A
00/20706	12/1999	WO	N/A
00/47841	12/1999	WO	N/A
0063510	12/1999	WO	N/A
01/02669	12/2000	WO	N/A
01/02672	12/2000	WO	N/A
0102670	12/2000	WO	N/A
01/07729	12/2000	WO	N/A
01/09461	12/2000	WO	N/A
01/47724	12/2000	WO	N/A
01/47725	12/2000	WO	N/A

01/48333	12/2000	WO	N/A
01/51732	12/2000	WO	N/A
01/53628	12/2000	WO	N/A
01/66877	12/2000	WO	N/A
01/75247	12/2000	WO	N/A
01/83488	12/2000	WO	N/A
01/96688	12/2000	WO	N/A
01/96689	12/2000	WO	N/A
01/98604	12/2000	WO	N/A
0198603	12/2000	WO	N/A
02/00449	12/2001	WO	N/A
02/04206	12/2001	WO	N/A
0208542	12/2001	WO	N/A
2002/055809	12/2001	WO	N/A
2002/055810	12/2001	WO	N/A
02/092342	12/2001	WO	N/A
03/012224	12/2002	WO	N/A
03/016654	12/2002	WO	N/A
03/016655	12/2002	WO	N/A
03/031750	12/2002	WO	N/A
03078761	12/2002	WO	N/A
03/083234	12/2002	WO	N/A
03/087497	12/2002	WO	N/A
03/089736	12/2002	WO	N/A
2004/015221	12/2003	WO	N/A
2004/020764	12/2003	WO	N/A
2004/037502	12/2003	WO	N/A
2004/042168	12/2003	WO	N/A
2004/063491	12/2003	WO	N/A
2004/079130	12/2003	WO	N/A
2004/083557	12/2003	WO	N/A
2004/085765	12/2003	WO	N/A
2005/002817	12/2004	WO	N/A
2005/018833	12/2004	WO	N/A
2005/033204	12/2004	WO	N/A
2005044536	12/2004	WO	N/A
2005/054597	12/2004	WO	N/A
2005/054599	12/2004	WO	N/A
2005054600	12/2004	WO	N/A
2005/068747	12/2004	WO	N/A
200588029	12/2004	WO	N/A
2005/098163	12/2004	WO	N/A
2006/033706	12/2005	WO	N/A
2006/042148	12/2005	WO	N/A
2006/043893	12/2005	WO	N/A
2006/056172	12/2005	WO	N/A
2006/066776	12/2005	WO	N/A
2006/090287	12/2005	WO	N/A
2006/103565	12/2005	WO	N/A
2006/104436	12/2005	WO	N/A

2006113690	12/2005	WO	N/A
2006125306	12/2005	WO	N/A
2006133690	12/2005	WO	N/A
2007008139	12/2006	WO	N/A
2007/059967	12/2006	WO	N/A
2007/081267	12/2006	WO	N/A
2007/113676	12/2006	WO	N/A
2007/141605	12/2006	WO	N/A
2008/078181	12/2007	WO	N/A
2008/091045	12/2007	WO	N/A

OTHER PUBLICATIONS

Schreiben LG Düsseldorf, Sep. 26, 2018, 7 pages. cited by applicant

Notice of Opposition to EP14188952.7, Jan. 4, 2018, 32 pages. cited by applicant

Acknowledgment of Receipt of Notice of Opposition to EP14188952.7, Jan. 4, 2018, 563 pages. cited by applicant

Klage, Sep. 20, 2018, 19 pages. cited by applicant

Declaration of Ann-Christine Ayed, May 29, 2019, 108 pages. cited by applicant

Prosecution History for U.S. Pat. No. 9,200,460, 6683 pages. cited by applicant

IPR for U.S. Pat. No. 9,200,460, 1026 pages. cited by applicant

International Search Report from International PCT Application No. PCT/IB2007/000862, mailed Apr. 18, 2008. cited by applicant

Chang et al., “Advances in Polyurethane Coatings (1969 to Early 1972)”, Product Review, Industrial & Engineering Chemistry Product Research and Development, vol. 12, No. 4, 1973. cited by applicant

Database WPI / Thomson Scientific, XP002621436, Feb. 16, 2011. cited by applicant

European Office Action from EP Application No. 14188952.7, Apr. 12, 2017. cited by applicant

Beitz et al., “Paperback for the Mechanical Engineering,” Dubbel, 1990, pp. 58-59. cited by applicant

European Patent Opposition from EP Application No. 14188952.7, Jan. 4, 2018. cited by applicant

European Patent Opposition from EP Application No. 14188952.7, Dec. 19, 2018. cited by applicant

Petition for Inter Partes Review of U.S. Pat. No. 9,200,460, May 30, 2019. cited by applicant

Beitz et al., “Paperback for the Mechanical Engineering,” Dubbel, as early as Jan. 1, 1990, 7 pages. cited by applicant

Curriculum Vitae of Ms. Ann-Christine Ayed in Support of Petition for Inter Partes Review of U.S. Pat. No. 9,200,460, May 29, 2019, 3 pages. cited by applicant

Decision from European Patent Office from Corresponding Patent Application No. EP17165499.9, Mar. 29, 2023. cited by applicant

Primary Examiner: Nguyen; Chi Q

Attorney, Agent or Firm: Workman Nydegger

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a continuation of U.S. application Ser. No. 18/169,498, filed Feb. 15, 2023, now U.S. Pat. No. 11,933,055, which is a continuation of U.S. application Ser. No. 17/195,876, filed Mar. 9, 2021, now U.S. Pat. No.

11,680,414, which is a continuation of U.S. application Ser. No. 15/930,629, filed May 13, 2020, now U.S. Pat. No. 10,975,578, which is a continuation of U.S. application Ser. No. 16/670,722, filed Oct. 31, 2019, now U.S. Pat. No. 10,745,921, which is a continuation of U.S. application Ser. No. 16/510,433 filed Jul. 12, 2019, now U.S. Pat. No. 10,519,674 which is a continuation of U.S. application Ser. No. 16/160,120 filed Oct. 15, 2018, now U.S. Pat. No. 10,358,831, which is a continuation of U.S. application Ser. No. 15/866,932 filed Jan. 10, 2018, now U.S. Pat. No. 10,125,499, which is a continuation of U.S. application Ser. No. 15/623,484 filed Jun. 15, 2017, now U.S. Pat. No. 9,890,542, which is a continuation of U.S. application Ser. No. 15/342,490 filed Nov. 3, 2016, now U.S. Pat. No. 9,695,599, which is a continuation of U.S. application Ser. No. 15/151,106 filed May 10, 2016, now U.S. Pat. No. 9,487,957, which is a continuation of U.S. application Ser. No. 14/672,444 filed Mar. 30, 2015, now U.S. Pat. No. 9,366,037, which is a continuation of U.S. application Ser. No. 12/303,044 filed Dec. 1, 2008, now U.S. Pat. No. 8,991,055.

BACKGROUND OF THE INVENTION

1. Field of the Invention

(1) This invention relates to a floor covering, to a floor element with which such floor covering can be composed, as well as to a method for manufacturing floor elements.

2. Related Art

(2) Amongst others, the invention relates to floor elements comprising a substrate and a top layer, or to floor coverings composed of such floor elements. Herein, this may relate to the type of floor elements known from the DE 203 10 959 U1, the substrate of which is composed of laths, which substantially consist of softwood and wherein the top layer thereof consists of wood, such as floor elements with a top layer of veneer or with a wooden top layer with a thickness between 1 and 15 millimeters. However, the invention is not restricted to the above-mentioned type of floor elements, but on the contrary also may relate to laminate floor panels having a top layer based on synthetic material, or to still other types of floor elements, for example, floor elements comprising a decorative element of natural stone, baked stone or ceramics, such as, for example, those known from the EP 1 441 086.

(3) It is known that such floor elements may be applied for forming a floating floor covering. Herein, these floor elements or floor panels, when being installed, are coupled at their edges, either by means of a conventional tongue and groove connection, wherein they possibly are glued into each other, or by means of mechanical coupling parts and locking parts providing, for example, in horizontal as well as in vertical directions for a locking of the floor elements, for example, such as described in the international patent application WO 97/47834.

SUMMARY OF THE DISCLOSURE

(4) In general, the present invention, according to all of its aspects, aims at a floor covering or floor elements having, allowing, respectively, a better and/or sturdier and/or simpler to manufacture coupling among adjacent floor elements in a floor covering.

(5) According to its first aspect, the invention relates to a floor covering of the kind consisting of floor elements, which, at least at a first pair of two opposite sides, comprise coupling parts, which substantially are performed as a male coupling part and a female coupling part, which are provided with vertically active locking portions, which, when the coupling parts of two of such floor elements cooperate with each other, effect a locking in vertical direction, perpendicular to the plane of the floor elements, and also are provided with horizontally active locking portions, which, when the coupling parts of two of such floor elements cooperate with each other, effect a locking in horizontal direction, perpendicular to the respective sides and in the plane of the floor covering, wherein said coupling parts are of the type allowing that two of such floor elements can be connected to each other at said sides by pushing one of these floor elements with the associated male coupling part, by means of a downward movement, home into the female coupling part of the

other floor element. In English, a connection by means of such downward movement is better known by the denomination of "push-lock".

(6) Coupling parts with associated locking portions allowing to mutually connect floor elements by bringing them towards each other by means of a downward movement are known, amongst others, from DE 10 2004 012 582 A1. A floor covering composed of floor elements with such coupling parts and locking portions, however, shows a limited strength of the locking, in particular of the locking in vertical direction, and has a relatively high risk of the coupling coming loose, even with a normal use of the floor covering.

(7) From WO 01/98604 and DE 101 38 285, it is known to implement the male coupling part of such floor elements with a vertical active locking portion in the form of a bendable lip-shaped portion, which elastically bends during the downward coupling movement and thereby performs a turning movement in order to spring back at the end of the coupling action and to get seated in an undercut of the female coupling part. However, the embodiments known from these documents still show a number of disadvantages. The embodiment of WO 01/98604, for example, shows the disadvantage that the male coupling part is made in a V-shape, such that the bendable lip-shaped portion is supported in a relatively weak manner and the locking shows a limited strength. Under the influence of a vertical pressure load onto the connection, for example, when walking thereon, a V-shaped coupling part may deform and a height difference may develop between two adjacent floor panels; under the influence of a horizontal tension load, for example, when the floor elements crimp in dry periods, a V-shaped male coupling part also may deform and there is an increased risk that a gap forms between two adjacent floor panels. In both patent documents, WO 01/98604 and DE 101 38 285, the bendable lip-shaped portion moreover is implemented on a separate edge portion, which is integrated into the substrate of the floor panels in a relatively weak manner.

(8) Other examples of such coupling parts and locking portions are known from WO 2005/054599 and EP 1 650 375. Here, too, use is made of a deformable portion, however, not of a bendable lip-shaped portion, for the vertically active locking portion. The deformable portion known from this document is made, as a whole, as a movable insert, which, during the downward coupling movement, is intended to perform a translation movement in its seat. This requirement concurrently effects that this deformable portion or this insert is integrated in the substrate of the respective floor elements in a weak manner. Moreover, due to the translation movement forces may occur having a splitting effect onto the substrate of the floor element, whereby in such floor element, in particular when coupling it repeatedly, the strength of the coupling may be lost.

(9) With the intention of restricting, amongst others, the risk of said coming loose or providing, in general, a better coupling among floor elements in a floor covering, wherein preferably at least one of the above-mentioned prior art problems is solved, the present invention relates to a floor covering of the above-mentioned kind, with as a characteristic that the male coupling part has a downwardly directed recess dividing this coupling part into, on the one hand, an upwardly directed bendable lip-shaped first portion functioning as one of said vertically active locking portions, and, on the other hand, a more massive second portion, wherein these portions are made in one piece of one and the same material.

(10) Preferably, the more massive second portion shows a full structure over the majority of its height, and preferably over its entire height, however, it is not excluded that this more massive second portion comprises a hollow structure, wherein this hollow structure then preferably is constructed such that the second portion is acting more massive, in other words, sturdier, than the first portion, such that the second portion, when being coupled by means of the above-mentioned downward movement, preferably is deformed hardly or not at all.

(11) Preferably, the more massive portion, over the majority of its height, viewed in a horizontal cross-section, has a thickness that is larger than the thickness of the first portion, both thicknesses being measured in the same horizontal cross-section. Even better, the second portion, over the majority of its height, is at least two times thicker than the first portion. It is noted that in order to

determine the respective thicknesses, internal cavities as a result of a possible hollow structure in the respective portions must be regarded as massive and thus must be factored in entirely in order to determine the thickness, as long as the second portion, as aforementioned, is acting more massive than the first lip-shaped portion.

(12) By embodiments according to the first aspect, it is obtained, on the one hand, that the first portion is sufficiently flexible in order to perform the coupling action by means of the downward movement, whereas, on the other hand, it is obtained that this first portion is suspended on a sufficiently sturdy base, such that it will be substantially only the first portion, which, during and/or after coupling, is exposed to a bending or turning movement. According to the characteristics of the first aspect, the male coupling part clearly is not V-shaped and the above-mentioned risks and disadvantages brought about by a V-shaped coupling part are limited.

(13) Preferably, the bendable lip-shaped first portion is designed such that it can be bent or turned at least towards the second, more massive portion. With such embodiment, a coupling by means of a downward or substantially vertical movement is easier to obtain.

(14) The aforementioned horizontally active locking portions preferably are formed by, on the one hand, an upright locking portion at the female coupling part, and, on the other hand, a locking portion on the male coupling part cooperating therewith. Preferably, the horizontally active locking portion of the male coupling part forms part of the aforementioned, more massive second portion and is this horizontally active locking portion made in one piece in the same material with the second, more massive portion. In such case, a particularly accurate locking with a good strength of the connection may be obtained.

(15) The cooperation among two floor panels of the invention preferably shows at least one or a combination of two or more of the following three features: the feature that the cooperation of the vertically active locking portions consists at least in that, in the coupled condition of two of such floor elements, the bendable lip-shaped first portion, at its distal extremity, contacts a wall of the female coupling part; the feature that, in the coupled condition of two of such floor elements, the underside of the second more massive portion contacts a wall of the female coupling part; the feature that the cooperation of the horizontally active locking portions consists at least in that, in the coupled condition of two of such floor elements, the upright locking portion of the female coupling part contacts the horizontally active locking portion of the male coupling part.

(16) In the most preferred form of embodiment, the cooperation among two floor elements shows all features mentioned herein above. This most preferred form of embodiment allows forming a floor covering according to the first aspect, with a high quality of the coupling of such floor elements that has been obtained in this manner.

(17) It is clear that in the cooperation among two floor elements preferably also at least one contact is formed at the height of the upper edges of the respective floor elements. It is noted that the coupling parts preferably allow that after coupling, a play-free, or anyhow at least almost play-free, connection among two of such floor elements is obtained.

(18) According to an important form of embodiment, the floor elements, at the side comprising the aforementioned male coupling part, are provided with a separate edge portion, in which the aforementioned first portion and the aforementioned second portion are made in one piece.

(19) According to said first aspect of the invention, as well as according to all the following aspects of the invention, in which a separate edge portion is mentioned, by such "separate edge portion" is meant that the edge portion is provided separately, with the intention of performing at least the coupling function, and that the floor element, globally seen, substantially is constructed of other portions or other material than the aforementioned separate edge portion. It is noted that such separate edge portion may be designed as a separate portion, which, for example, is or can be mechanically connected to the actual floor panel, as well as can be designed as a portion, which industrially is fixedly connected to the actual floor panel at least by means of another connection technique, such as by means of adhering or by integration into a possible substrate of the floor

element.

(20) By providing such edge portion, the material of this edge portion can be entirely adapted to its desired function, for example, amongst others, that of coupling, whereas the remaining portions of the floor element can be made of the materials being usual for the respective type of floor panel. The fact that the second portion is more massive in this case allows obtaining a better integration of the separate edge portion with the floor element.

(21) According to an example of this important form of embodiment, the aforementioned separate edge portion may be realized as an insert, meaning that it has been provided in or at the floor panel as one fixed whole. Herein, it is possible that the aforementioned edge portion, insert, respectively, forms the entire respective side of the floor element, preferably with the exception of a possible top layer and/or backing layer and/or other globally horizontal-extending layers, such as sound-damping layers being, for example, of the type as known from WO 03/016655. It is also possible that such separate edge portion is provided at both of said first pair of opposite sides, wherein then preferably also the female coupling part is realized at least partially, and still better including the aforementioned vertically and horizontally active locking portions, in the respective separate edge portion.

(22) In general, it is noted that synthetic material is particularly suited for forming the aforementioned material of which the first and second portions are made in one piece. Synthetic material allows realizing the first lip-shaped first portion with small dimensions, while still retaining a sufficient elastic bending ability thereof for the coupling action. Preferably, this relates to a synthetic material on the basis of polyurethane and/or on the basis of a fully reacted polyurethane/isocyanate composition. The application of such materials is particularly useful when the aforementioned material relates to the material of a separate edge portion, such as that of an insert or of a separate edge portion provided on the floor element in any manner. Synthetic material, such as material on the basis of polyurethane and/or on the basis of a fully reacted polyurethane/isocyanate composition, is also extremely suitable for providing said separate edge portion by means of casting or injection molding at the floor element, wherein it is not excluded that, by the same casting process, also other portions are provided on and/or in the floor element.

(23) Said coupling parts and/or locking portions may be formed in any manner. So, for example, they may be formed as milled profiles, as extruded profiles, or by a combination of extrusion and a machining treatment, such as milling or the like. When said coupling parts and locking portions are formed as milled profiles, it is preferred that the milling treatment takes place while the aforementioned material, in which the bendable lip-shaped first portion and the second portion are made in one piece, already is provided in or on the floor element, and even better, in order to obtain a high accuracy, in the same milling treatment at least also the upper edge of the respective side of the floor element is formed. By such technique, higher precisions are obtained than by a technique, wherein an already formed profile is provided as an insert in the substrate of the floor elements. By "the same milling treatment", it is not necessarily intended that the upper edge is formed with the same milling tools, however, that the reference frame in which this milling treatment takes place is the same reference frame as the one in which the profiles are formed.

(24) When the aforementioned coupling parts and locking portions are formed as extruded profiles, use can also be made of the technique of co-extruding, wherein several synthetic materials together are extruded to one massive whole.

(25) According to the first aspect and the other aspects described hereafter, the floor elements of the present invention can be formed according to a plurality of possibilities.

(26) According to a first possibility, the aforementioned floor panels may be formed as floor panels with a substrate substantially consisting of wood or wood-based materials, wherein then preferably a separate edge portion is provided at least at one side of the substrate, wherein said bendable first portion and the second, more massive portion are made in one piece.

(27) Examples of wood or wood based materials are spruce wood or other types of softwood,

chipboard, fiberboard, MDF or HDF (Medium Density Fiberboard or High Density Fiberboard). In the case of materials such as spruce wood or other softwood, these materials preferably are present in the substrate in the form of adjacent-situated laths.

(28) According to said first possibility, the floor elements may relate to floor panels with a wooden top layer, such as a top layer of veneer or of a layer of wood from 1 to 15 millimeters, such as, for example, prefabricated parquet, wherein then preferably also a wooden backing layer is present at the bottom side of the floor panels. So, for example, may the respective floor panels be of the type that comprises a substrate composed of adjacent-situated laths, wherein on this substrate a wooden top layer, whether or not composed of several parts, is provided, whereas a backing layer is provided against the bottom side of this substrate, said separate edge portion being formed by means of one of the aforementioned laths, to which aim this lath consists of a material, preferably a material containing synthetic material, wherein this material differs from the material of which the majority of the other laths is made, wherein it is not excluded that the material of the majority of the other laths also may comprise synthetic material. Floor panels with a wooden top layer, the substrate of which comprises wooden or wood-based portions, such as laths, are better known in English under the generic denomination “engineered wood”. When in such floor element, said backing layer is omitted and the floor element thus substantially consists of the substrate, possibly constructed of said laths, and the wooden top layer, this relates to dual layer parquet, which is known better under the German denomination of “Zweischichtparkett”.

(29) According to the same first possibility, the respective floor panels may be of the type that comprises a substrate and wherein the separate edge portion forms part of a material part situated in a groove-shaped recess in the edge of the substrate. Herein, this may relate, for example, to floor elements with a top layer on the basis of synthetic material, as it is the case, for example, with laminate flooring. In such laminate flooring, the top layer of the floor panels may comprise carrier sheets immersed in resin or in synthetic material, said sheets consisting, for example, of paper, wherein at least one of these carrier sheets shows a printed décor that is visible at the upper side of the floor panels and forms a so-called decorative layer. Preferably, with such floor panels also a backing layer on the basis of such resin-impregnated carrier sheet is provided at the bottom side thereof. In laminate flooring, for the actual substrate preferably use is made of MDF or HDF.

(30) Of course, the floor element, according to this first possibility, also may relate to a floor element substantially consisting of a massive wooden floor panel, wherein then preferably a separate edge portion is provided at least at one side of this floor panel.

(31) As aforementioned, in the first possibility preferably use is made of a separate edge portion. With such configuration, during the aforementioned bending or turning movement of the bendable lip-shaped first portion, a reduced or almost no splitting effect is exerted on the actual substrate of the floor element, which is particularly important for wood-based substrates, such as substrates of MDF or HDF.

(32) According to a second possibility, the aforementioned floor elements may be formed as tiles showing at least a decorative element of real ceramics, baked stone or natural stone. Herein, this may relate to floor elements of the type known from EP 1 441 086 or to any other floor element comprising a decorative element of real ceramics, baked stone or natural stone.

(33) According to a second independent aspect, the invention also relates to a floor covering of the kind mentioned in relation to the first aspect, with the characteristic that the floor elements comprise a substrate and a top layer, wherein the male coupling part is at least partially formed on a separate edge portion, preferably an insertion part, which is present in the substrate at the respective side, and the male coupling part has a downwardly directed recess, said recess, dividing this coupling part into, on the one hand, bordering an upwardly directed bendable lip-shaped first portion at the male coupling part; that the separate edge portion comprises a basic portion with which this edge portion is seated at least partially in the actual floor panel, such that this basic portion, at the upper side as well as at the lower side, is bordered by the remaining material of the

floor element; and that, seen in vertical section through the basic portion and the surrounding material, the basic portion extends over a distance being at least half of the thickness of the substrate.

(34) According to this second independent aspect, an improved integration of the separate edge portion, the insert, respectively, in the floor element is obtained. This may be of importance, for example, in the case that the respective coupling parts and/or locking portions in the separate edge portion or insert are realized as milled profiles, whereas the separate edge portion is already provided in or at the substrate, as with such treatment, forces are exerted onto the separate edge portion or insert, which forces might pull it out of its desired position in the substrate. Therefore, a good integration of the separate edge portion or the insert is important for achieving a good precision when forming the coupling parts and/or locking portions.

(35) Such good integration is also of importance in the case of the occurrence of a horizontal tension load on the connection. As aforementioned, such tension load may occur when the floor elements are subjected to crimping, for example, in dry periods.

(36) It is preferred that, viewed in said vertical cross-section, said distance is at least 60 percent, and still better at least 70 percent, of the thickness of the substrate. Optimally, said distance, viewed in said vertical cross-section, is between 80 and 100 percent of the thickness of the substrate.

(37) According to the second aspect, it is not necessary to make the separate edge portion of only one material. An important example of the second aspect relates to a floor element, the separate edge portion of which in fact is made in one piece, however, comprises various materials, such as this is the case, for example, with a separate edge portion made by co-extrusion. Such separate edge portion, for example, enables making said second portion substantially of a less clastic material than the first portion, whereas they both are situated on the same separate edge portion.

(38) According to an important form of embodiment, a horizontally active coupling portion is situated at the male coupling part, said coupling portion also being situated in the separate edge portion, wherein said basic portion, in respect to the floor element, is situated more proximally than said horizontally active locking portion. Preferably, this relates to a horizontally active locking portion of the type that can cooperate with an upright horizontally active locking portion of the female coupling part.

(39) It is clear that this second aspect can be performed in a beneficial manner in combination with the characteristics of said first aspect and its preferred forms of embodiment.

(40) According to a third independent aspect, the present invention also relates to a floor covering of the kind discussed in the first aspect, with as a characteristic that at least one of both coupling parts, either the male coupling part or the female coupling part, has a recess that divides this coupling part into, on the one hand, an inwardly bendable lip-shaped first portion functioning as one of the aforementioned vertically active locking portions, and, on the other hand, a second portion, wherein the, in respect to the respective floor panel, proximal flank of the recess extends from the base of the recess towards the opening of the recess inclined towards the outer edge of the floor element. Preferably, the in respect to the floor element distally-situated flank of the recess herein forms a flank of said first portion.

(41) According to the third aspect, the recess is made such that, for bending or turning said first portion, a free space is obtained consisting at least partially of an undercut, whereby said first portion can bend or turn at least with its distal end, if this should be necessary, during coupling by means of a downward movement as far as underneath the top surface of the respective floor element.

(42) Said proximal flank may serve as a stop surface for the first portion, such that this latter does not lose its resiliency by bending or turning too far in the coupling process, or when performing the coupling process repeatedly, which is beneficial to the strength of the coupling.

(43) In a preferred form of embodiment, the turning point of the lip-shaped first portion, anyhow, at least in the not coupled condition, is situated vertically underneath the top surface of the respective

floor panel, which exerts a beneficial influence onto the coupling by means of a downward movement.

(44) In the most important forms of embodiment of the third aspect, the coupling part forming said recess is the male coupling part. Herein, most beneficially said recess is directed downward, whereas the bendable lip-shaped first portion is directed upward. In such case, it is desirable to provide for that the extension of said proximal flank of the recess extends farther than the upper edge of the respective floor element or just touches this upper edge. In this manner, it is obtained that the recess is simple to realize as a milled profile, as a recess with these features to be realized is better accessible to a milling tool. Moreover, that part of the lip-shaped first portion that, in not coupled condition, extends farther than the upper edge of the respective floor element can be kept limited, whereas still a sufficient bending or turning ability of the lip-shaped portion can be obtained.

(45) When, in other forms of embodiments, the coupling part having the recess is the female coupling part, said recess preferably is directed upward, whereas the bendable lip-shaped first portion is directed downward.

(46) In respect to the degree of inclination of said proximal flank of the recess, an inclination forming an acute angle of 10° with the vertical may suffice. However, preferably this relates to a larger angle, such as an angle of 30° or more, even if it is preferable to provide for this angle being smaller than 70° .

(47) Of course, the characteristics of the third aspect may also be of importance with a floor covering with the characteristics of said first and/or second aspects.

(48) According to a fourth independent aspect, the present invention also relates to a floor covering of the kind mentioned in the first aspect, with as a characteristic that the floor elements comprise a wooden or wood-based actual substrate and a top layer, wherein at least one of both coupling parts, either the male coupling part with its associated locking portions, or the female coupling part with its associated locking portions, are formed entirely on a separate edge portion of synthetic material, preferably an insert of synthetic material, which is present in the substrate at the respective side, whereas the coupling part at the opposite side is formed at least partially, and preferably entirely, in the wooden or wood-based actual substrate.

(49) In a preferred form of embodiment of this fourth independent aspect, it is the side having the male coupling part at which the coupling parts and locking portions are formed entirely on a separate edge portion or insert of synthetic material.

(50) The inventive idea of applying synthetic material at a side of a floor element offers improved possibilities for realizing coupling parts and locking portions allowing that two of such floor elements can be connected to each other by moving them towards each other by a downward movement. So, for example, may the bendable lip-shaped first portion mentioned in the first, second and third aspects be performed with improved features such, that an improved coupling is obtained. Also, applying a separate edge portion of synthetic material, such as a plastic insert, at the opposite sides as well may be redundant and may involve unnecessary costs and operations. Therefore, according to the fourth aspect, the coupling parts and locking portions at the opposite side are made at least partially, and preferably entirely, of an inexpensive and/or easy to process material, such as wood or wood-based material.

(51) The use of synthetic material also allows applying coupling parts and locking portions that are realized in another manner than milled profiles. Thus, for example, they may be realized as extruded profiles. This technique allows a very large constructional freedom.

(52) This fourth aspect is very useful when realized in combination with the first, second and/or third aspects. Herein, it is clear that then preferably the side carrying the coupling part with the bendable lip-shaped first portion is entirely made of synthetic material, possibly with the exception of a top layer and/or backing layer present at the floor element.

(53) It is noted that the inventive idea of the invention disclosed by means of the fourth aspect,

namely the application of a separate edge portion of synthetic material for realizing coupling parts and locking portions, may also find a broader application. The additional constructional freedom that can be obtained with such a material also is advantageous with other kinds of floor coverings than those disclosed by means of the first to the fourth aspects. So, for example, may this idea also be of importance for floor coverings of which the floor elements are composed to a more complex laying pattern, such as a herringbone pattern.

(54) From WO 2004/063491 is known how more complex laying patterns, such as a herringbone pattern, can be realized by means of two kinds of floor elements, which differ from each other in that they are made in a mirrored manner, anyhow, at least in respect to the coupling parts and locking portions thereof.

(55) From WO 2005/098163 moreover in the meantime is known how such more complex laying pattern may also be realized with only one kind of floor elements. A precondition for being able to form more complex laying patterns, such as a herringbone pattern with only one kind of floor elements, is that both sides of a first pair of opposite sides of a first floor element can cooperate with both sides of a second pair of opposite sides of a second floor element. As is evident from the forms of embodiment in WO 2005/098163, this precondition rapidly leads to complex coupling profiles which are difficult to provide directly in the substrate, in particular when this substrate is made of wood or wood-based material, such as MDF or HDF.

(56) According to its fifth independent aspect, the present invention relates to floor coverings that are composed of floor elements allowing the realization of more complex laying patterns, however, the coupling profiles of which are simpler to realize. To this aim, the present invention relates to a floor covering composed of floor elements with a first pair of opposite sides and a second pair of opposite long sides, wherein the floor elements, at the first pair of opposite sides as well as at the second pair of opposite sides, comprise coupling parts, wherein the coupling parts situated at the second pair of opposite sides substantially are made as a male coupling part and a female coupling part and respectively can cooperate with the female coupling part and the male coupling part of the second pair of opposite sides of an identical floor element, and wherein the coupling parts of both opposite sides of the first pair of sides are designed such that each of these coupling parts can cooperate with the male coupling part as well as with the female coupling part of the second pair of opposite sides of an identical second floor element, with as a characteristic that the coupling parts situated at the first pair of opposite sides of the floor elements are made at least partially, and preferably entirely, of a synthetic material. It is clear that the floor covering of the fifth aspect preferably is composed in a herringbone pattern.

(57) Preferably, the floor covering of the fifth aspect is composed of rectangular oblong floor elements, wherein the short sides of these floor elements determine the aforementioned first pair of opposite sides and wherein the long sides of these floor elements determine the aforementioned second pair of opposite sides.

(58) According to an important form of embodiment of the fifth aspect, the floor elements comprise at least a substrate, whether or not consisting of several parts, and a top layer, wherein the substrate substantially consists of wood or wood-based materials, and the coupling parts situated at the aforementioned second pair of opposite sides of the floor elements are integrally formed in this wood or wood-based material, whereas the coupling parts situated at both sides of the aforementioned first pair of opposite sides of the floor elements are formed in separate plastic edge parts, which latter are provided at the respective sides of the floor elements.

(59) Said male coupling part and female coupling part can be provided with vertically active and horizontally active locking portions, such that, in the aforementioned cooperation of the second pair of sides of two identical floor elements, a mutual locking is present in vertical direction, by means of the vertically active locking portions, as well as in horizontal direction, by means of the horizontally active locking portions. The coupling parts situated at both sides of the first pair of opposite sides of a floor element can also be provided with vertically active and horizontally active

locking portions, such that in the aforementioned cooperation with the male coupling part, as well as in the aforementioned cooperation with the female coupling part of the second pair of sides of an identical floor element, there is a mutual locking in a vertical direction, by means of the vertically active locking portions, as well as in horizontal direction, by means of the horizontally active locking portions.

(60) According to a sixth independent aspect, the invention also relates to a method for manufacturing floor elements, which comprise at least a decorative element defining at least partially the upper side of the respective floor element, and which have coupling parts at least at two opposite sides, wherein the floor elements, at least at one of these sides, are provided with a separate edge portion of synthetic material, whereas the floor elements, globally seen, are constructed of another material than the material of the edge portion, with as a characteristic that the method comprises at least the following two successive steps:

(61) the step of producing a semi-finished product comprising at least said edge portion and said decorative element, wherein the edge portion, when producing the semi-finished product, already is provided or is being provided with a portion of the coupling part to be formed therein; the step of performing a machining treatment on the separate edge portion of an already formed semi-finished product in order to fabricate at least a portion of the coupling part to be formed therein.

(62) It is noted that by "successive steps" is meant that the machining treatment takes place after the semi-finished product has been produced and it is, thus, not excluded that in between these successive steps, one or more other manufacturing steps take place.

(63) The machining treatment preferably consists at least of a milling process, for example, with rotating milling tools. A very suitable synthetic material for this application is a synthetic material comprising polyurethane and/or produced on the basis of a mixture of polyurethane and isocyanate. Further, use can also be made of filled synthetic material composites, such as extruded wood, which comprises wood fibers and/or wood chips as a filling material. The composition of such material may be optimally adapted to the milling process and the profile to be realized. Moreover, when treating extruded wood, the same milling tools may be used as when processing a wood-based material, such as MDF or HDF. In that the milling technology is the same as or similar to the usual technology for fabricating wooden or wood-based floor elements, switching to extruded wood is possible for flooring manufacturers without many difficulties or high costs.

(64) According to a first possibility, when producing the semi-finished product, said edge portion is provided in the semi-finished product as an insert. In an important application of this first possibility, the semi-finished product is produced by bringing together wooden or wood-based laths with the aforementioned separate edge portion of synthetic material and providing the decorative element as a top layer on these laths and edge portion, wherein preferably also a backing layer is provided underneath these laths and edge portion. Preferably, said separate edge portion also is performed as a lath.

(65) According to a second possibility, when producing said semi-finished product, said edge portion is realized at least partially by providing a solidifying substance at the respective side; for example, this substance may be provided by spraying. This solidifying substance preferably comprises at least an elastomer on the basis of polyurethane, such as, for example, a synthetic material provided on the basis of a mixture of polyurethane and isocyanate. It is also possible that, for example, extruded wood is directly formed on or extruded onto the semi-finished product.

(66) According to this second possibility, for example, said edge portion may be realized by casting or at least partially encapsulating the decorative element into synthetic material, such as polyurethane, or filled synthetic material. In this manner, for example, such decorative element, for example, a tile, may be provided at its edges and possibly also at its bottom with synthetic material by such casting process. Possibly, said bottom may form a carrier structure for the decorative element. It is noted that the encapsulated decorative elements as such are known, for example, from WO 2006/042148.

(67) The first as well as the second of the hereinabove mentioned possibilities may be applied when, for producing the semi-finished product, one starts from a board-shaped material, upon which the decorative element is provided as a top layer, and wherein said edge portion in which the machining treatment is performed, is provided at this board-shaped material, thus, when this board-shaped material already is provided with a top layer. This board-shaped material may have been formed in a preceding step as a board of laminate material with a top layer on the basis of synthetic material, such as a top layer on the basis resin-immersed carrier sheets of paper. For forming the board of laminate material, for example, use may be made of a DPL (Direct Pressure Laminate) process, wherein the top layer is provided by pressing the respective resin-immersed carrier sheets together with the basic board at an increased temperature.

(68) The aforementioned first possibility may, for example, also be applied when the semi-finished product is composed by bringing together wooden and/or wood-based laths with the separate edge portion, which then preferably is also present as a lath, in order to form a substrate, or anyhow at least a portion of a substrate, and providing a decorative layer, for example, in the form of a wooden top layer, as a top layer on this substrate, wherein it is desirable that also a backing layer is provided below these laths and edge portion. By such method, for example, “engineered wood” floor panels can be manufactured with a separated edge portion or insert, in which the coupling parts are provided, said portion or insert being integrated at least at one side thereof, preferably at least at one of the short sides of an oblong floor panel.

(69) According to still another form of embodiment of this sixth aspect, it is possible that the method is applied for manufacturing a floor element, wherein said semi-finished product substantially is formed of a tile or the like of a stone-like material, at which then, directly or indirectly, said separate edge portion of synthetic material is provided. Herein, the stone-like material may relate, for example, to natural stone, artificial stone, baked stone, ceramics or the like.

(70) Preferably, the method is used for manufacturing floor panels of the type of which said coupling parts formed by means of the machining treatment allow that two of such floor elements can be interconnected at the respective sides by pushing one of these floor elements, by means of a downward movement, home into the other floor element. It is in particular with floor elements of this type that the application of a separate edge portion of synthetic material or filled synthetic material composite offers advantages. The coupling of two floor elements by means of a downward movement takes place most beneficially when the coupling parts have relatively thin bendable portions. Thus, these portions preferably are made in said synthetic material of the separate edge portion, as synthetic material or filled synthetic material composite allows for a larger constructional freedom than the usual wood-based materials, such as MDF or HDF.

(71) Of course, the method of the sixth aspect is very suitable for realizing the floor elements of which the floor coverings of the first through the fifth aspect are composed. In the case that the method is applied for realizing floor elements that can be composed to floor coverings with the characteristics of the first through the third aspect, preferably at least said bendable lip-shaped first portion intended to function as a locking portion and/or said recess are formed by means of the machining treatment, more particularly at least by means of a milling process by means of rotating milling tools.

(72) According to a seventh independent aspect, the invention also aims at a floor covering of the type mentioned in the first aspect, which is easy to manufacture and/or induces a series of new possibilities for such floor coverings and/or the floor elements of which they are composed. More particularly, it is possible to obtain, by means of such floor elements, connections by means of a so-called “push-lock”, which are stronger and/or can be applied more broadly. To this aim, the invention relates to a floor covering of the above-mentioned type, with as a characteristic that at least one of the coupling parts, either the male coupling part or the female coupling part, is at least partially made of a filled synthetic material composite, preferably a fiber-filled synthetic material composite.

(73) The composition of such synthetic material composites may be adapted to the design, the appearance and/or the required functionality of the final respective coupling part. So, for example, may the synthetic material contents or the type of synthetic material be adapted according to the required flexibility, or the filling material or the form thereof may be chosen according to the desired strength or rigidity, namely, Young's modulus, of the composite. Possibly, such synthetic material composite may also comprise at least two zones of different composition. Such zones may be obtained, for example, by means of co-extrusion. Further, also the color of such synthetic material easily can be adapted. A highly suitable filled synthetic material composite for application in a floor covering according to this seventh aspect is a composite, the filling material of which contains wood fibers and/or wood chips, such as this is the case with extruded wood. However, other filling materials may be applied, too. In the case of a fiber-filled synthetic material, the fibers also may be substantially formed by hemp fibers. Others than the aforementioned organic filling materials are possible, too, such as glass fibers, as well as inorganic filling materials are possible, such as glass fiber, carbon fibers and the like.

(74) As a synthetic material, for example, a thermoplastic material may be applied in said composite, preferably a polyester, such as polyethylene terephthalate (PET), which, for example, may be recycled from waste material. Also, a synthetic material, such as polyethylene, polypropylene, polystyrene, polycarbonate or polyvinylchloride may be chosen. All of these synthetic materials allow keeping the temperature during extruding relatively low, such that the applied filling material is not affected. It is evident that this temperature depends on the type of filling material. For wood chips or wood fibers, one may work, for example, with an extrusion temperature between 100 and 200° C., and still better between 120 and 150° C. The mixing ratios between the applied synthetic material and the applied filling material preferably are between 70/30 and 20/80. Further examples of such materials are described, for example, in WO 2005/033204 or WO 2005/002817.

(75) It is noted that synthetic material composites filled with wood chips and/or wood fibers may show an appearance or a touch that approaches real wood or other wood-based materials, such as MDF. The presence of such material thus may render the product more trustworthy to the users than the presence of a material with the appearance of synthetic material.

(76) The floor elements of such floor covering may be implemented in various manners.

(77) According to a first possibility, said floor elements comprise at least a substrate and a separate edge portion, preferably an insert. Herein, said filled synthetic material composite may be present at least in said separate edge portion and/or this separate edge portion or insert consists of filled synthetic material composite. Further, said separate edge portion or insert may form the entire respective side of the floor element, with the exception of a possible top layer and/or a backing layer that may be present at the substrate.

(78) Still according to this first possibility, the actual substrate of the floor element may substantially consist of one or more other materials than said filled synthetic material or may not at all consist of filled synthetic material. So, for example, for the actual substrate use may be made of softwood, such as spruce wood, chipboard, fiberboard, MDF or HDF.

(79) According to a particular preferred form of embodiment of this first possibility, said floor elements are formed as floor panels with a substrate that substantially consists of wood or wood-based materials, wherein then preferably at least at one side of the substrate a separate edge portion of filled synthetic material is provided, in which the respective coupling part is made in one piece. The respective floor elements may be, for example, of the type of "engineered wood" or, more particularly, of the type which comprises a substrate that is composed of adjacent-situated laths, wherein on this substrate a wooden top layer, whether or not composed of several parts, is provided, wherein the separate edge portion is formed by means of one of said laths, wherein the respective lath is constructed of filled synthetic material. Possibly, also a backing layer may be provided against the underside of this substrate. If this backing layer is absent, then in the technical

jargon one is speaking of “tweelaagsparket” (in English: dual layer parquet; in German: Zweischichtparkett). It is clear that in such floor covering, too, the application of a separate edge portion of filled synthetic composite can be desirable.

(80) According to a second possibility, said floor elements comprise at least a substrate, wherein this substrate substantially consists of said fiber-filled synthetic material composite. Of course, such substrate can be provided with a top layer and/or a backing layer. Examples of top layers are wooden top layers, such as veneer, or decorative films and other layers comprising a printed décor, such as laminate layers of the DPL (Direct Pressure Laminate) or HPL (High Pressure Laminate) type. Preferably, said substrate forms at least one side and preferably both sides of said first and/or second pair of opposite sides.

(81) In the floor elements of the seventh aspect, the respective coupling part may entirely or partially be made of said filled synthetic material composite. Also, both coupling parts, the male coupling part as well as the female coupling part, may have at least a portion that is made of said filled synthetic material composite. Also, they may both be made entirely of this synthetic material composite.

(82) The floor elements of the seventh aspect may be rectangular, wherein then preferably the first pair of opposite sides forms the short sides of the floor elements and thus such filled synthetic material composite is applied at least at one of these short sides. It is clear that the floor elements also may have a second pair of opposite sides, which also are provided with mutually cooperating coupling parts, which substantially are made as a male and a female coupling part, which are provided with vertically active locking portions and horizontally active locking portions. Two of such floor elements may be connected to each other at said second pair of opposite sides by pushing one of these floor elements with the associated male coupling part, by means of a downward movement, home into the female coupling part of the other floor element. It is possible that the coupling parts of the second pair of opposite sides have characteristics identical to those of the coupling parts and locking portions of the first pair of opposite sides. However, other connection methods or characteristics are not excluded for this second pair. For example, it is possible that the coupling parts of the second pair of opposite sides, additionally or solely allow interconnecting two of such floor elements at this pair of sides by providing one of these floor elements with the associated male coupling part, by means of a turning movement and/or by means of a horizontal shifting movement, in the female coupling part of the other floor element.

(83) Said coupling parts of the seventh aspect may be formed, for example, as milled and/or extruded profiles. In the case of said first possibility and in the case that a milling treatment is applied, it is preferred that the final shape of the respective coupling part, which at least partially is made in filled synthetic material composite, is obtained by this milling treatment, while the separate edge portion or insert is already situated at the floor element or a semi-finished product thereof. Possibly, this edge portion already may show the global shape of the respective coupling part prior to its connection with the floor element, for example, in that the filled synthetic material has been extruded and/or pre-milled as such. However, according to the invention it is not excluded that the coupling parts are formed entirely in the insert or separate edge portion prior to connecting this edge portion with the floor element. This may take place by any technique, for example, by milling and/or extruding.

(84) It is noted that the present invention also relates to floor panels that are obtained by applying the method of the sixth aspect. Also, the present invention relates to floor panels that can be applied for composing a floor covering with the characteristics of the first, the second, the third, the fourth, the fifth and/or the seventh aspects.

(85) Further, it is noted that, according to the invention, pushing the male coupling part, by means of a downward movement, home into the female coupling part, anyhow, at least in respect to the embodiments according to the first through the third aspects, implies that said bendable lip-shaped first portion always is a bendable portion providing for a snap-on and/or engaging action. Also with

other “push-locks”, preferably a snap-on and/or engaging action takes place. However, this snap-on and/or engaging action does not necessarily have to be realized by means of a lip-shaped portion, but may also be realized by means of any bendable and/or deformable portion, which is present at least at one of the respective sides to be coupled. Such portion may be present at the male coupling part as well as at the female coupling part. So, for example, may a bendable portion be formed at least by a portion of the female coupling part that projects beyond the upper edge of the respective side. Instead of working with a bendable portion, one may also work with a compressible portion, which then is compressed at least temporarily at least during the coupling action. This deformation or compression may at least partially relax at the end of the coupling action and, as a result of the volume increase of the respective portion of, for example, the male and/or the female coupling part, may take part in the obtained horizontal and/or vertical locking.

(86) Preferably, according to all aspects of the invention, the coupling parts and locking portions are made such that, in a coupled condition of two of such floor elements, a locking exists that is operative in all directions of the plane perpendicular to the longitudinal direction of the coupled edges.

(87) Further preferred forms of embodiment of the first through the seventh aspects will be described by means of the figures and the appended claims, and a further particular aspect of the invention will be explained as well.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) With the intention of better showing the characteristics of the invention, hereafter, as an example without any limitative character, several preferred forms of embodiment are described, with reference to the accompanying drawings, wherein:
- (2) FIG. 1 represents a floor panel for composing a floor covering with, amongst others, the characteristics of the first, second, third, and fourth aspects of the present invention;
- (3) FIG. 2 in cross-section represents a view according to the line II-II indicated in FIG. 1;
- (4) FIG. 3 represents the application of the floor panel from FIG. 1;
- (5) FIG. 4 in cross-section represents a view according to the line IV-IV indicated in FIG. 1;
- (6) FIGS. 5 to 7 further illustrate the application of the floor panel from FIG. 1, wherein
- (7) FIG. 6, at a larger scale, represents a view of the portion indicated by F6 in FIG. 5, and
- (8) FIG. 7, also at a larger scale, represents a view of the portion indicated by F7 in FIG. 2;
- (9) FIGS. 8 to 15 represent variants of the floor panel from FIG. 1, wherein FIG. 14 at a larger scale represents a view on the portion indicated by F14 in FIG. 9;
- (10) FIGS. 16 to 18 represent a floor covering with the characteristics of the fifth aspect, wherein FIGS. 17 and 18 respectively represent a view according to the lines XVII-XVII and XVIII-XVIII, as indicated in FIG. 16;
- (11) FIGS. 19 and 20 represent a variant of such floor covering in views similar to those of FIGS. 17 and 18;
- (12) FIGS. 21 and 22 illustrate methods with the characteristics of the sixth aspect of the present invention, wherein FIG. 22 represents a variant for the portion indicated by F22 in FIG. 21;
- (13) FIGS. 23 and 24 represent views according to the lines XXIII-XXIII and XXIV-XXIV, respectively, indicated in FIG. 22;
- (14) FIGS. 25 and 26 represent variants of a method according to the sixth aspect of the invention in a view similar to that of FIG. 23;
- (15) FIGS. 27 to 29 further illustrate how a method with the characteristics of the sixth aspect can be performed; and
- (16) FIGS. 30 to 33, in a view similar to that of FIGS. 8 to 13, represent examples of floor

coverings showing, amongst others, the characteristics of the seventh aspect of the invention.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS OF THE INVENTION

(17) FIG. 1 represents a floor element 1 for forming a floor covering according to the invention. In this case, this relates to a rectangular and oblong floor element 1 that can be applied for composing a floor covering with, amongst others, the characteristics of the first, second, third and fourth aspects of the present invention.

(18) As is illustrated by means of FIG. 2, the floor element 1 comprises a substrate 2, a top layer 3 and, in this case, also a backing layer 4. According to the invention, the top layer 3 and the backing layer 4 may consist of any material. So, for example, may the top layer 3 consist of wood, such as veneer or a layer of wood with a thickness from 1 to 15 millimeters, as it is the case here, and, in the case that a backing layer 4 is present, this backing layer 4 may also consist of wood. The represented floor element 1 relates to a floor element of the type that is better known under the denomination “prefabricated parquet” or “engineered wood”. Such type of floor panel is also known, for example, from DE 203 10 959 U1 mentioned in the introduction. In this type of floor panel, the substrate 2 may comprise portions 5 consisting of wood or wood-based material, such as spruce wood or another type of softwood, chipboard, fiberboard, MDF or HDF. In the example of FIG. 1, these portions 5 are formed as laths 6 extending, adjacent to each other, with their longitudinal direction into the transverse direction of the floor element 1.

(19) At a first pair of opposite sides 7-8, in this case the short sides, the floor panel has coupling parts 9-10, which can cooperate with each other and which substantially are made as a male coupling part 9 and a female coupling part 10. The coupling parts 9-10 are also provided with vertically active locking portions 11-12 and horizontally active locking portions 13-14.

(20) By means of these coupling parts 9-10 and associated locking portions 11-12-13-14, as FIG. 3 shows, two of such floor panels 1 can be interconnected by pushing one of these floor elements 1 with the associated male coupling part 9, by means of a downward movement 15, home into the female coupling part 10 of the other floor element 1 and, in the joined condition of two of such floor elements 1, a locking is obtained in a vertical direction V1 by means of the aforementioned vertically active locking portions 11-12, as well as in a horizontal direction H1 by means of the aforementioned horizontally active locking portions 13-14.

(21) According to the first aspect, the floor element 1 of the example shows the particular characteristic that the male coupling part 9 has a downwardly directed recess 16, said recess dividing this coupling part 9 into, on the one hand, an upwardly directed bendable lip-shaped first portion 17 functioning as one of the aforementioned vertically active locking portions 11, and, on the other hand, a more massive second portion 18, wherein these portions 17-18 are made in one piece of one and the same material. As indicated in FIG. 2, the second portion 18 herein, over the majority of its height HM, viewed in a horizontal cross-section H, has a thickness TM that is larger than the thickness TF of the first portion 17, both aforementioned thicknesses TF-TM being measured in the same horizontal cross-section H. In the example, the second portion 18 over the majority of its height even is more than twice as thick as the first portion 17.

(22) In this case, the aforementioned first portion 17 and second portion 18 are made in one piece in a separate edge portion 19, which is provided at the respective side 7 and is realized as an insert 20 in the actual substrate 2. Here, the separate edge portion 19, just like the remaining portions 5 of the substrate 2, is formed as a lath 6. Herein, the edge portion 19 forms the entire respective side 7 of the floor element 1, with the exception of the top layer 3 and the backing layer 4.

(23) In general, according to all aspects of the present invention, it is preferable that the floor elements 1 have a substrate 2, said substrate 2 comprising portions 5 consisting of wood or wood-based material, such as spruce wood or another type of softwood, chipboard, fiberboard, MDF or HDF.

(24) It is noted that, of course, it is not excluded that at the opposite side 8, on which the female coupling part 10 is formed, also a separate edge portion 19, such as an insert 20, can be present,

upon which the female coupling part **10** then is formed at least partially and preferably entirely. The separate edge portions **19** or inserts **20** applied at both opposite sides **7-8** may be manufactured from the same as well as from a differing material. Preferably, at least one of both edge portions **19** consists of synthetic material. In the example of FIGS. **1** to **3**, the side **7** having the male coupling part **9** comprises an insert **10** of synthetic material.

(25) Apart from the dimensions of the separate edge portion **19** or insert **20**, and apart from the thickness TF-TM of the first portion **17** and the second portion **18**, the backing layer **4**, which may be provided at the underside **21** of the floor elements **1**, and/or the top layer **3**, such as in this case, preferably extend at least partially underneath, above, respectively, the separate edge portion **19** or insert **20**, or anyhow at least partially underneath, above, respectively, said second portion **18** of the male coupling part **9**.

(26) The floor element **1** represented in the FIGS. **1** to **3** may also be applied for forming a floor covering with the characteristics of the aforementioned second aspect of the invention. To this aim, the separate edge portion **19** has a basic portion **22**, with which this edge portion **19** is seated in the actual floor panel **1**, such that this basic portion **22** is bordered at the underside, in this case, by the backing layer **4**, as well as at the upper side, in this case by the top layer **3**, by the remaining material of the floor element **1**. Viewed in the vertical section V through this basic portion **22** and the surrounding remaining material, the basic portion **22** extends over a distance DM being at least one half of the thickness TS of the substrate **2**. In this case, viewed in the vertical section V, the substrate **2** is formed substantially, and in this case, entirely, by the aforementioned insert **20**.

(27) FIG. **3** clearly shows that with the respective floor element **1** or floor panel also a floor covering **23** may be formed with the characteristics of the third aspect of the invention. To this aim, the flank **24** of said recess **16**, said flank being proximally situated in respect to the floor element, extends from the base **25** of the recess **16** towards the opening **26** thereof in an inclined manner towards the exterior edge of the floor panel **1**. Herein, the acute angle A formed by this flank **24** with the vertical is more than 10° and less than 70° , namely 30° .

(28) The acute angle B formed by the global center line **27** of the lip-shaped first portion with the vertical preferably is smaller than said angle A. A particularly good value for B lies in the order of magnitude of 15 to 25° . This order of magnitude for the angle B allows a smooth coupling by means of said downward movement **15**.

(29) As aforementioned, the here applied insert **20** at the side **7** having the male coupling part **9** consists of synthetic material, whereas the aforementioned female coupling part **10** is formed of another portion **5** of the substrate **2**, preferably a wooden or wood-based portion **5** of this substrate **2**. In such case, it is namely obtained that the floor element **1** or floor panel can also be applied for forming a floor covering **23** with the characteristics of the fourth aspect of the invention.

(30) As also mentioned above, FIG. **3** clearly illustrates the coupling action by which two floor elements **1** can be mutually coupled by moving them in a downward direction towards each other, as indicated by arrows **15**. As indicated, it is not excluded that said downward coupling movement **15** deviates from the vertical and has a horizontal component HC. According to the invention, however, the vertical component VC of the downward coupling movement **15** will dominate. When performing this coupling movement **15** with the floor elements **1** or floor panels of the example, the bendable lip-shaped first portion **17** performs a turning movement towards the second, more massive portion **18**, in order to spring back entirely or partially at the end of the coupling action, in this case into an undercut **28** of the female coupling part **10**, and wherein the lip-shaped first portion **17** and the undercut **28** then in this way function as said vertically active locking portions **11**, **12**, respectively. The turning point O of said turning movement preferably, as illustrated herein, is situated vertically underneath the upper surface **29** of the respective floor element **1**.

(31) FIG. **3** also shows that the cooperation of the vertically active locking portions **11-12**, in this case the lip-shaped first portion **17** and the undercut **28**, consists at least in that the bendable lip-shaped portion at its distal end **30** makes a contact **31** with a wall **32** of the female coupling part **10**,

namely the wall **32** bordering the undercut **28** towards the top.

(32) The cooperation between both floor elements **1** in the floor covering **23** also results in the fact that at the underside **33** of the more massive second portion **18** a contact **34** is formed with the female coupling part **10**. Also, a contact **35** is formed at the height of the horizontally active locking portions **13-14**, which, in the present case, are performed as, on the one hand, an upright locking portion **36** at the female coupling part **10**, and, on the other hand, a coupling portion **37** cooperating therewith at the male coupling part **9**. Herein, the respective contact **35** takes place on a flank **38** of the locking portion **37** at the male coupling part **9**. Preferably, this flank **38**, at the height of the contact **35**, is made with an inclination that forms an angle L with the horizontal, said angle differing from 90° and being larger than 45°. The larger the angle L is made, the sturdier the horizontal connection may be. The angle L illustrated here is 60°.

(33) It is noted that in the example, the aforementioned horizontally active locking portion **13-37** of the male coupling part **9** forms part of the aforementioned more massive second portion **18** and is made in one piece with this second portion, in the same material, and thus, in this case, is made in the same separate edge portion **19** as the first portion **17** and the second portion **18**.

(34) Further, it is noted that, in the example of FIG. 2, the aforementioned flank **38** of the horizontally active locking portion **37** borders a recess **39**. In such case, the distal end **30** of the lip-shaped first portion **17** most beneficially is situated in a horizontal plane extending at a distance D above the lowermost point of said recess **39**. Preferably, this distance D is chosen between forty and seventy percent of the height HF of the lip-shaped portion **17**. In the example represented here, the distance D is approximately one half of this height HF.

(35) In principle, the aforementioned bendable lip-shaped first portion **17** may have any shape. Its thickness TF may vary in function of the height HF or remain constant. However, preferably the thickness TF of this portion **17** will decrease towards the distal end **30** thereof.

(36) Further, it is possible that in the coupled condition of two floor elements **1**, the projecting lip **40** bordering the female coupling part **10** towards the bottom is bent out over a small distance P. Due to the resiliency of this bent-out lip **40**, a tension is created in the connection, said tension forcing the male coupling part **9** and the female coupling part **10** towards each other. Such tension is also known as a “pretension” and is described, for example, in WO 97/47834.

(37) FIG. 4 shows that, according to all aspects of the invention, also the second pair of opposite sides **41-42**, in this case the long sides of the floor element **1** of FIG. 1, can be provided with cooperating coupling parts **9-10**, which substantially are made as a male coupling part **9** and a female coupling part **10**, which are provided with vertically active locking portions **11-12** and horizontally active locking portions **13-14**. The illustrated coupling parts **9-10** and locking portions **11-12-13-14** are of the type as is known from the WO 97/47834 and allow that the floor elements **1** can be connected at this pair of sides **41-42** at least by providing one of these floor elements **1** with the associated male coupling part **9**, by means of a turning movement W, in the female coupling part **10** of the other floor element **1**, such as depicted with the dashed line **43**. Other types of coupling parts and locking portions at the second pair of opposite sides **41-42** of a floor element **1** according to the invention are possible. So, for example, it is possible to favor coupling parts and locking portions that allow that the floor elements can be connected to each other at least by shifting them towards each other in the horizontal direction H1, or which allow that the floor elements can be connected to each other at least by moving them towards each other in a downward, substantially vertical direction V1. In this latter case, it is possible to choose at the second pair of opposite sides **41-42** coupling parts and locking portions that have characteristics identical to those of the coupling parts **9-10** and locking portions **11-12-13-14** of the first pair of opposite sides **7-8**.

(38) As FIGS. 5 and 6 indicate, the possibility of connecting the floor elements **1** at their second pair of opposite sides **41-42** by turning them into each other enables a fast and simple installation. In such case, the user only has to perform a single movement, namely the turning movement W,

with the floor elements **1**. Namely, by turning the floor element **1** into each other at said second pair of opposite sides **41-42**, automatically a downward movement **15** is obtained at the first pair of sides **7-8**, whereby these, too, are coupled. By means of this downward movement **15**, the male coupling part **9** of the respective floor element **1** can be pushed home into the female coupling part **10** of a floor element **1** already installed in the same row **44**. The user only has to provide for that the male coupling part **9** is situated at the first pair of opposite sides **7-8** above the female coupling part **10**. It is noted that in the case of floor coverings **23** with the characteristics of the present invention, this positioning of the male coupling part **9** is not so critical, as the inventors have found that, at the end of the coupling action, it is possible that the male coupling part **9**, to a limited extent, in the horizontal direction **H1** automatically pulls itself into the female coupling part **10**.

(39) FIG. **7** illustrates that the bendable lip-shaped first portion **17**, in a preferred form of embodiment of the invention according to all of its aspects, in the connected condition of two of such floor elements **1**, has sprung back only partially and remains standing against the wall **32** bordering said undercut **28** of the female coupling part **10** in upward direction. In dashed lines **45-46**, in FIG. **7** the position of the first portion **17** respectively before and during the coupling action is represented. As the lip-shaped first portion **17** in the coupled condition, which is represented in full line, has sprung back only partially, a clamping effect of the coupling is provided, such that then a good vertical locking is obtained. Such clamping effect may best be obtained by performing the aforementioned wall **32** bordering the undercut **28** in upward direction with an inclination, and preferably performing it such that the turning circle **C** of the first lip-shaped portion **17**, or the curve describing the possible positions of the distal extremity **30** of this lip-shaped first portion **17**, on the one hand, has at least a first point **C1**, which, viewed in the vertical plane through the upper edge **47** of the floor panel, is situated underneath the aforementioned wall **32** or the extension **48** thereof, and, on the other hand, has at least a second point **C2**, where said curve or turning circle **C** intersects said wall **32**. As already mentioned above, the turning circle **C** of the circle approaching the turning curve preferably, as herein, has a center **O** situated vertically underneath the upper surface **29** of the respective floor element **1**.

(40) FIG. **8** shows a variant with the characteristics of the third and the fourth aspect of the invention. Herein, contrary to floor coverings **23** with the characteristics of, for example, the first and/or the second aspects, the coupling part having said recess **16** is the female coupling part **10**, and said recess **16** is directed upward, whereas the bendable lip-shaped first portion **17** is directed downward.

(41) The female coupling part **10** and its associated locking portions **12-14** are performed on a separate edge portion **19**, such as an insert **20**, in this case made of synthetic material, whereas the male coupling part **9** is entirely formed in a wooden or wood-based portion **5** of the actual substrate **2**.

(42) It is noted that the female coupling part **10** of the example preferably is fabricated by means of an extrusion technique.

(43) FIG. **9** shows a variant, wherein said separate edge portion **19** or insert **20** remains visible at the upper surface **29** of the floor covering **23** after coupling two of such floor elements **1**. There, the insert may, for example, fulfill a decorative function, such as imitating a cement joint or a rubber strip **49**, such as with the imitation of ships' decks. However, it is not excluded that the insert **20** at the upper surface **29** also fulfills a technical function, for example, the function of a seal counteracting the penetration of water into the connection.

(44) It is noted that in the example of FIG. **9**, the separate edge portion **19** forms the entire respective side **7** of the floor element **1**, with the exception of the backing layer **4**.

(45) FIG. **10** shows another variant, in which, at the upper edges **47** of the floor elements **1**, a material portion **50** has been removed in order to form a chamfer **51**, in this case, a bevel. Such chamfer **51** may also continue as far as into the substrate **2** or the separate edge portion **19**, and may possibly be covered with a separate decorative layer. Here, an embodiment with a covered chamfer

is not represented. However, chamfers **51**, which are provided with a separate decorative covering, are known those skilled in the art, for example, from WO 01/96689.

(46) A further variant is represented in dashed line **52** in FIG. **10**, wherein the first lip-shaped portion **17** also functions as a horizontally active locking portion, whether or not in a limited manner.

(47) FIG. **11** represents another preferable form of embodiment of the first through the fourth aspects of the invention. This relates to a floor covering **23**, which is composed of floor elements **1**, the substrate **2** of which is formed of a board **53** of, for example, MDF or HDF, whether or not already provided with a top layer **3** and/or backing layer **4**, where at least at one of two opposite sides **7-8**, and preferably at both opposite sides of that pair, material has been removed and said separate edge portion **19** forms part of a material part situated in the obtained groove-shaped recess **54** in the edge of the substrate **2**. The separate edge portion **19** is, for example, glued into the substrate **2** as an insert **20**, or is formed within the groove-shaped recess **54** by means of an injection molding technique. In dashed line, also a variant **19A** for the separate edge portion **19** is represented, having an attachment portion with which it can be integrated even sturdier into the substrate **2**.

(48) The form of embodiment of FIG. **11** is particularly suited for laminate floor panels manufactured by means of a DPL (Direct Pressure Laminate) process. With such floor panels, the top layer **4**, as represented here, is constructed of carrier sheets **55**, for example, paper sheets, immersed in synthetic material or resin, which are consolidated in a heated press with a board material **53**, such as an MDF or HDF board. At the underside **21** of the board material **53**, also a carrier sheet **55** immersed in synthetic material or resin is provided as a backing layer **4** by means of the same press treatment. The board **53** obtained by means of the press treatment then is divided into panels having approximately the size of the final floor panels or floor elements **1**. Preferably, it is in these panels **1** that, as aforementioned, material is removed from the board material in order to form the groove-shaped recess **54**, in which the separate edge portion **19-19A** is realized, preferably as an insert **20**.

(49) One of the aforementioned carrier sheets **55** that are situated at the upper side **29** of the floor element, is a decorative layer **55A** with a printed décor, which, for example, represents a wood pattern. This decorative layer **55A** is protected against wear and/or scratching by means of a wear-resistant layer **55B**, which latter also comprises such resin-immersed carrier sheet **55**, and is known better under the denomination of an overlay. The wear resistance of this latter carrier sheet **55B** may have been obtained, for example, in that it contains hard particles, such as aluminum oxide and/or silicon carbide.

(50) As aforementioned, the form of embodiment of FIG. **11**, amongst others, has the characteristics of the second aspect. Viewed in the vertical section V, the basis portion **22** of the separate edge portion or insert **20** extends over a distance DM that is more than one half of the thickness TS of the substrate **2**. In this vertical section V, the separate edge portion **19**, at its underside as well at its upper side, is bordered by the actual substrate **3**, which, in this case, relates to the board-shaped material **53**.

(51) FIG. **12** represents another variant, wherein the recess **39**, which is bordered by the horizontally active locking portion **37** in the male coupling part **9**, has only a limited depth. Herein, the deepest point of this recess **39** is situated in an horizontal plane situated below the deepest point of the recess **16** in the separate edge portion **19**. In this manner, a particularly massive second portion **18** is obtained.

(52) FIG. **13** shows a variant, in which the separate edge portion **19** has a hollow structure **56**; however, the aforementioned second portion **18** still acts more massive compared to the lip-shaped first portion **17**.

(53) FIG. **14** shows a possible application of a co-extruded separate edge portion **19** or insert **20**. In the example, the separate edge portion **19** consists of, on the one hand, a first material **57** with

which the separate edge portion **19** adjoins against the adjacent floor element **1**, and which, after coupling two of such floor elements **1**, also remains visible at the upper surface **29**, and, on the other hand, of a second material **58** that has been extruded together with the first material **57** and forms the remaining portion of the separate edge portion **19**. For the first material **57**, for example, a rubber can be chosen, such that a good protection against the penetration of moisture into the connection is obtained, whereas for the second material **58** a synthetic material on the basis of polyurethane can be chosen, which, as mentioned herein above, is extremely suited for realizing milled profiles. Of course, it is not excluded that in such co-extruded separate edge portion **19** more than two materials are combined. It is noted that co-extrusion may also be performed in filled synthetic material composites, such as extruded wood.

(54) FIG. **15** shows a variant of a floor covering **23** with the characteristics of, amongst others, the first and the third aspect of the invention. The floor elements **1** represented here relate to floor elements formed as tiles and comprising a decorative element **59** of a stone-like material, such as real ceramics. At both sides of at least a first pair of opposite sides **7-8** of the floor elements, a separate edge portion **19** of synthetic material is provided. To this aim, in the example, groove-shaped recesses **54** are provided at the decorative element **59**, in which the respective separate edge portion **19** can be provided, in this case by means of a snap-on coupling. According to a not-represented variant, such decorative element **59** also may be at least partially encapsulated by means of synthetic material, such as polyurethane, or filled synthetic material composite, such as extruded wood. With such encapsulation, preferably at the underside of the decorative element **59** a bottom is formed and at least at one side and preferably at all sides an edge portion is formed, in which then coupling parts may be provided, for example, by means of a milling process.

(55) FIGS. **16** through **20** represent floor coverings **23** with the characteristics of the fifth aspect of the invention, mentioned in the introduction.

(56) The example of FIG. **16** relates to a floor covering **22** composed in a herringbone pattern.

(57) As represented in the FIGS. **17** and **18**, the floor elements of the floor covering **23** of FIG. **16** comprise coupling parts at a first pair of opposite sides **7-8**, namely, at the short sides, as well as at a second pair of opposite sides **41-42**, namely at the long sides of the floor elements **1**. The coupling parts **9-10** of the pair of opposite long sides **41-42** substantially are performed as a male coupling part **9** and a female coupling part **10**, which, as is illustrated in FIG. **18**, may cooperate with the female coupling part **10** and the male coupling part **9**, respectively, of the opposite long sides **41-42** of an identical floor element. The coupling parts **60** of both opposite short sides **7-8** of the floor elements **1**, as is illustrated in FIG. **17**, are designed such that each of these coupling parts **60** can cooperate with the male coupling part **9**, as well as with the female coupling part **10** of opposite long sides **41-42** of an identical floor element **1**.

(58) The particularity of the floor elements represented in the FIGS. **17** and **18** consists in that the coupling parts **60** situated at the opposite short sides **7-8** of the floor elements **1** are made at least partially and preferably entirely of a synthetic material, such as a filled synthetic material composite or any other synthetic material, such as, for example, polyurethane. At both sides of a first pair of opposite sides **7-8** of the floor elements **1**, in this case, the short sides, a separate edge portion **19** or insert **20** of synthetic material is provided in the substrate **2**. Herein, in the example, the separate edge portions **19** or inserts **20** form the entire respective sides **7-8** of the floor elements **1**, with the exception of the top layer **3** and the backing layer **4**. On the separate edge portions **19**, coupling parts **60** and/or locking portions **61** are formed, which can cooperate with the coupling parts **9-10** and/or the locking portions **11-12-13-14** of both sides **41-42** of the second pair of opposite sides. Preferably, the coupling parts **60** and locking portions **61** at the first pair of opposite sides **7-8**, as illustrated herein, are made identical, whereas the coupling parts **9-10** at the second pair of opposite sides **41-42** substantially are made as a tongue at the side **41** having the male coupling part **9** and a groove at the side **42** having the female coupling part **10**. The mutual cooperation among the coupling parts **9-10** of the second pair of opposite sides **41-42** is represented

in FIG. 18.

(59) In the example of the FIGS. 17 and 18, the aforementioned tongue is provided with two locking elements 37 at its underside, namely, on the one hand, a first locking element 37A situated proximally in respect to the respective floor element 1 and allowing the tongue to cooperate with an upright locking portion 36 of the female locking part 10 or the groove at the opposite side 42, and, on the other hand, a second locking element 37B allowing the male coupling part 9 or the tongue to cooperate with one of the upright locking elements 62 of the first pair of opposite sides 7-8.

(60) Herein, it is noted that, in the example of the FIGS. 17 and 18, in the cooperation of one side of the first pair of opposite sides 7-8 with the female coupling part 10 or the groove of the second pair of opposite sides 42, solely a locking in the horizontal direction H1 is achieved, whereas in a cooperation of that side with the tongue of the second pair of opposite sides a locking in the horizontal direction H1 as well as in the vertical direction V1 is achieved.

(61) In a similar view as that of FIGS. 17 and 18, FIGS. 19 and 20 show that it is not excluded to provide coupling parts 60 and locking portions 61, which, when cooperating with a male coupling part 9 as well as with a female coupling part 10, effect a locking in the horizontal direction H1 as well as in the vertical direction V1. In the example, use is made of a bendable lip-shaped portion 17, which, as in the examples of FIGS. 2, 3, and 7 through 15, functions as a vertically active locking portion and is obtained in that a recess 16 divides the respective coupling part 60 or the separate edge portion 19 on which this coupling part 60 is provided, into this lip-shaped bendable first portion 17 and a second portion 18, which in this case is made more massive than the first portion 17. It is clear that the illustrated coupling parts 60 and locking portions 61 also have or may have other features in common with those of the aforementioned figures and that these features here, too, are useful.

(62) FIG. 21 illustrates several steps of a method with the characteristics of the sixth aspect of the invention. This relates to a method for manufacturing floor elements 1, which comprise a decorative element 59 and have coupling parts at least at two opposite sides, and in this case at all opposite sides. In the example of FIG. 21, the decorative element 59 relates to a decorative element 59 in the form of a wooden top layer 4 defining the upper surface 29 of the floor element 1.

(63) More particularly, the method relates to a method for manufacturing floor panels or floor elements 1 of the type represented in FIG. 1, with an actual substrate 2 comprising wooden or wood-based portions 5, with a top layer 3 and a backing layer 4 of wood and a separate edge portion 19 of synthetic material, said edge portion being provided at least at one side 7. It is noted that, globally seen, the floor element 1 is constructed of another material than the synthetic material of the separate edge portion 19.

(64) According to the sixth aspect, the method comprises at least a step in which a semi-finished product 63 is produced, which comprises at least said edge portion 19 and said decorative element 59.

(65) In the example, the semi-finished product 63 is produced by bringing together wooden or wood-based laths 6 and the aforementioned separate edge portion 19 of synthetic material and providing the decorative element 59 as a top layer 3 on these laths 6 and edge portion 19, wherein preferably, as represented herein, also a backing layer 4 is provided underneath said laths 6 and edge portion 19. In this case, the separate edge portion 19 relates to an insert 20 also in the form of a lath 6. As indicated by the dashed line 64, it is not excluded that both opposite sides 7-8 are provided with a separate edge portion 19 or insert 20, wherein then it is possible that both edge portions 19 consist of synthetic material, however, it is not excluded that solely one thereof is an edge portion 19 or insert 20 of synthetic material, whereas the other edge portion 19, for example, is an edge portion consisting of a wood or wood-based material, such as MDF or HDF, preferably also in the form of a lath 6.

(66) It is noted that combining wooden or wood-based laths 6 with, for example, an insert 20 of MDF or HDF is known to manufacturers of the type of floor elements mentioned in the

introduction, which is known by the denomination of “engineered wood” and described, amongst others, in DE 203 10 959 U1. However, the inventors have found that by inserting an insert **20** of synthetic material instead of an MDF insert, a plurality of new possibilities is created. So, for example, the floor elements **1** of floor panels mentioned in connection with the first through the fifth aspects can be manufactured in a smooth manner on similar or even on the same machines already applied by existing manufacturers of floor elements **1** or floor panels. These manufacturers do not need to provide special machines. Preferably, however, care is taken when choosing the synthetic material that the dust created by the machining treatment of the sixth aspect can be mixed with the dust occurring as a result of a possible machining treatment of the remainder of the floor element, such that the waste streams remain governable in a simple manner. Ideally, in respect to governing the waste streams, extruded wood may be applied as a synthetic material. Moreover, such material may be processed by means of the same or similar tools as wood or wood-based materials, such as MDF or HDF.

(67) Further, it is noted that by means of such method also a floor element **1** can be formed of the type “dual layer parquet” or “Zweischichtparkett”. For forming such floor element **1**, said backing layer may be omitted, such that the obtained floor element **1** substantially consists of said laths **6**, insert **20** and top layer **3**.

(68) As aforementioned, these new possibilities show their advantages in particular with coupling parts **9-10** and locking portions **11-12-13-14** allowing interconnecting two floor elements **1** by means of a downward movement **15**.

(69) After the semi-finished product **63** has been provided, the step of performing a machining treatment takes place at the separate edge portion **19** of the already formed semi-finished product in order to fabricate at least a portion of the coupling part **9-10-60** to be formed therein. To this aim, in the example, the obtained semi-finished product **63**, with its underside **21** directed upward, is conveyed through two edge profiling machines **65** and is provided with coupling parts **9-10-60** and/or locking portions **11-12-13-14-61** at its opposite long sides **41-42**, as well as at its opposite short sides **7-8**, by means of a milling process being said machining treatment. Milling treatments at the edges of floor elements **1** are described, for example, in detail in the aforementioned WO 97/47834. The mechanical tools applied for the machining treatment preferably relate to rotating milling tools **66**.

(70) FIGS. **22** through **24** illustrate another method with the characteristics of the sixth aspect. Herein, this relates to a method wherein, for producing the semi-finished product **63**, one starts from a board-shaped material **53**, upon which the decorative element **59** already has been applied as a top layer **3**. In this example, a groove-shaped recess **54** is provided in the actual substrate **2** or board material **53** by means of a machining treatment. The separate edge portion **19**, in which the machining treatment of the sixth aspect is performed, is provided at this board-shaped material **53**, which already is provided with a top layer **3**, by providing it as an insert **20** in the groove-shaped recess **54**. The separate edge portion **19** is attached there, for example, by means of gluing.

(71) Thereafter, as described by means of FIG. **21**, follows the step of performing a machining treatment. It is noted that such method is recommended for laminate floor panels, such as, for example, the laminate floor panel represented in FIG. **11**.

(72) In the case of a floor covering having the characteristics of the first, second, third and/or fourth aspects, it is preferred that at least the bendable lip-shaped portion **17** and/or recess **16** mentioned in these aspects has been formed by means of said machining treatment.

(73) It is evident from FIG. **24** that chambers **67** may be present between the aforementioned separate edge portion **19** or insert **20** and the substrate **2**. These chambers **67** may be applied for providing glue **68** therein. Also, on the figure is represented in dashed line **69** that the insert **20** does not necessarily have to be provided completely matching into the actual substrate **2**. The excess material **70** is removed, for example, by said machining treatment when forming the coupling parts **9-10** and/or the locking portions **11-12-13-14**.

(74) FIG. 25 illustrates a method with the characteristics of the sixth aspect, wherein, when providing the semi-finished product **63**, the aforementioned separate edge portion **19** is realized at least partially by providing a solidifying substance **71** at the respective side. In the example of FIG. 25, the separate edge portion **19** is applied by spraying said substance **71** by means of a spraying head **72**. It is noted that the here applied, previously made, groove-shaped recess **54**, in which the separate edge portion **19** is provided, has an undercut. This undercut **73** promotes the adherence between the separate edge portion **19** of synthetic material and the remainder of the floor element **1**. Possibly, by means of the solidifying substance **71** also at least a partial encapsulation may be obtained, wherein then by means of this substance a bottom is provided at the floor element **1**, as well as, at least at one side and preferably at all sides, a separate edge portion is formed of the respective material.

(75) FIG. 26 illustrates another variant of a method with the characteristics of the sixth aspect, wherein said semi-finished product **63** substantially is formed of tile or the like of a stone-like material functioning as the decorative element **59**, at which then, directly or indirectly, said separate edge portion **19** is provided at least at one of the sides. In the example of FIG. 26, the separate edge portion **19** is provided by pushing it into the groove-shaped recess **54**, as represented by arrow **74**, where it is locked by means of a snap-on coupling. Here, too, for obtaining the separate edge portion **19** one may think of an at least partial encapsulation of the decorative element **59**.

(76) Of course, in the example of FIG. 25 as well as in the example of FIG. 26, after the step of providing the semi-finished product **63** follows the step of performing the machining treatment, as schematically represented in FIG. 21.

(77) FIGS. 27 to 29 show an example of such machining treatment to greater detail. The figures illustrate how the coupling parts **9-10** and locking portions **11-12-13-14** can be formed in successive machining treatment by means of rotating milling tools **66**, while the floor elements are resting on their upper surface **29**. The represented floor element **1** is a floor element **1** that can be applied for forming a floor covering **23** with the characteristics of the first through the fourth aspect.

(78) In the step of performing the milling treatment, preferably milling tools **66** are used having a diameter of at least 5 times the thickness of the floor elements **1**. In the example of the FIGS. 27 to 29, the milling tools **66** forming the male coupling part **9**, as well as the milling tools **66** forming the female coupling part **10**, rotate about rotation axes **75** forming at least two different angles with the upper surface **29**.

(79) FIG. 29 shows how, amongst others, in the first aspect said recess **16** may be formed by means of a rotating machining tool **66**. It is noted that herein, a proximal flank **24** of the recess **16**, said flank being inclined according to the third aspect, the extension of which extends beyond the upper edge **47** or just touches it, guarantees a good accessibility for the respective tool **66**.

(80) It is noted that floor elements **1** of floor coverings **23** with the characteristics of the first, second, third, fourth, fifth and/or seventh aspects at the respective sides **7-8** preferably may be removed from a floor covering **23** or can be uncoupled again, without requiring a tool to this aim and without thereby damaging the respective coupling parts **9-10**, such that they can be used several times. In the most practical forms of embodiment, the coupling parts and locking portions to this aim are made such that two of such floor elements can be uncoupled from each other by means of a turning movement, which applies to all embodiments represented in the figures.

(81) It is not excluded that, according to all herein above-mentioned aspects, the separate edge portion **19** is realized of a natural elastic material, such as natural rubber.

(82) Further, it is noted that according to all aspects of the invention, it is not excluded that said synthetic material also comprises other ingredients, such as ground wood particles, however, that preferably an excess of synthetic material is provided, such that said bending ability of the first lip-shaped portion **17** can be realized. So, for example, a modified wood fiber material may be used,

which comprises an excess of resin. Other highly suitable examples of such materials relate to the materials known as “fiber-filled synthetic material composites”, or more particularly “extruded wood”. Such materials are formed starting from a mixture of ground wood particles, such as fine wood chips and/or wood fibers, and synthetic material and, by means of an extrusion procedure, are formed to a solid material that is simple to process. Apart from the simple processing ability of these composite materials, they also may approach real wood or other wood-based materials in respect to appearance and/or touch, which renders such edge portion in a floor element more easily acceptable to the user. Apart from wood fibers, also the use of hemp fibers is possible, which show very good fiber geometry for such application. In the case of said filled synthetic material composite, viewed in cross-section, zones with different composition and/or features may be applied in order to obtain different features in different zones, for example, in respect to elasticity, color, adherence, smoothness of the surface, processability and the like. In a practical manner, this may be realized, amongst others, by means of co-extrusion. So, for example, the mixing ratio between synthetic material and filling material, for example, fiber material, such as wood fibers, may be adapted in the respective filled synthetic material composite according to the zone.

(83) From the above, it becomes clear that the present invention, according to a particular independent aspect thereof, also relates to a floor covering **23** consisting of floor elements **1**, which, at least at a first pair of two opposite sides **7-8**, comprise coupling parts **9-10**, which substantially are made as a male coupling part **9** and a female coupling part **10**, which are provided with vertically active locking portions **11-12**, which, when the coupling parts **9-10** of two of such floor elements **1** cooperate, effect a locking in the vertical direction VI, perpendicular to the plane of the floor elements **1**, as well as are provided with horizontally active locking portions **13-14**, which, when the coupling parts **9-10** of two of such floor elements **1** cooperate, effect a locking in the horizontal direction H1, perpendicular to respective sides **7-8** and in the plane of the floor covering **23**, with as a characteristic that the floor elements **1** comprise at least a substrate **2** and preferably also a top layer **3**, wherein at least one of said coupling parts at least partially is formed at a separate edge portion **19-20**, preferably an insert **20**, which is present at the respective side **7** in the substrate **2**, wherein this separate edge portion **19** consists of a filled, preferably a fiber-filled, synthetic material composite, whereas the actual substrate **2** of the floor element **1** substantially consists of one or more other materials. It is evident that advantages may already be achieved when only a portion of one coupling part is made of a filled synthetic material composite, however, that it is preferred that the entire respective coupling part is made of such filled synthetic material composite, and that even better the male as well as the female coupling part are constructed of such material, or anyhow are constructed at least for a part thereof of such material.

(84) Preferably, said fiber-filled synthetic material composite is extruded wood, wherein the filling material is formed by wood chips and/or wood fibers. It is clear that also other filling materials and/or synthetic materials can be applied. For other possible synthetic material composites, reference is made to the introduction, where such materials and their components are explained in connection with the seventh aspect.

(85) For the actual substrate **2**, use can be made of any, preferably wood-based material, for example softwood, such as spruce wood, chipboard, fiberboard, MDF or HDF.

(86) The application of this particular independent aspect is particularly interesting for the floor panels known under the denomination of “engineered wood” and of which the substrate **2** is composed of laths **6**. So, for example, may this aspect be applied in the embodiments represented in FIGS. **1** to **4**, wherein then, for example, the respective separate edge portions are made in said filled synthetic material composite. Such separate edge portions of filled synthetic material, preferably fiber-filled synthetic material, may also be applied in laminate floor panels, such as the one represented in FIG. **11**.

(87) This particular independent aspect best may be applied with oblong rectangular floor panels having a pair of long and a pair of short opposite sides. Herein, said separate edge portion of filled

synthetic material composite preferably is provided at least at one of the sides of the short pair and still better at least at both opposite short sides. Clearly, it is not excluded that such separate edge portion is also or solely applied at one or both opposite long sides.

(88) Further, it is clear that applying a filled synthetic material composite, such as extruded wood, is useful for providing coupling parts, independently of which type of mutual connection these coupling parts are allowing. So, for example, by means of such extruded wood, one or more coupling parts may be provided at a floor panel, said coupling parts allowing at least for a mutual connection with the coupling parts of another similar floor panel by means of a turning movement, a horizontal shifting movement and/or a downward pushing movement. The composition of filled synthetic materials can be adapted such that they allow forming the most complex profiles therein, for example, by means of a machining treatment, such as milling. Possibly, the respective profiles also may be formed entirely or partially by means of the extrusion process. In the most suitable composition of such filled synthetic material, an excess of synthetic material is applied, which means that a synthetic material/filling material ratio is applied, which is higher than 50:50. Of course, the invention does not exclude that an excess of the filling material, for example, of wood fibers and/or wood chips, might be applied. Further, possibly also the fiber length of the filling material can be adapted, for example, between 70 and 2500 micron. Also, the moisture percentage of the extruded wood may be adapted, for example, between 1 and 10%. Preferably, within the frame of the present invention wood fiber lengths between 100 and 1000 micron and/or moisture percentages lower than 7%, and still better lower than 5%, are handled. These adaptations of mixing ratio, fiber length and/or moisture content are also useful with said seventh aspect of the invention, as well as in all other aspects where such filled synthetic material can be applied.

(89) Of course, floor panels with the characteristics of this particular aspect also may show the characteristics of the first, second, third, fourth and/or seventh aspects. A method according to the sixth aspect, as, for example, illustrated in FIGS. 21 to 25, is recommended for the fabrication of the floor elements which can be applied for composing a floor covering with the characteristics of this particular independent aspect and/or the seventh aspect.

(90) FIG. 30 shows an example of a floor covering, which, amongst others, has the characteristics of said particular aspect of the invention and also shows the characteristics of said seventh aspect, and which is composed of floor elements 1 of the type “engineered wood”. The male coupling part 9 can be pushed, with a substantially downward movement, home into the female coupling part 10 in order to form a connection in horizontal direction H1 as well as in vertical direction V1. Herein, the female coupling part 10 of a so-called “push-lock” connection is made in a filled synthetic material, such as extruded wood. To this aim, at the respective side 8 of the floor element 1 a separate edge portion 19 in the form of an insert 20 of this filled synthetic material composite is provided, upon which the female coupling part 10 then is formed entirely, for example, by means of a method with the characteristics of the sixth aspect. The respective insert 20 forms the entire respective side 8 of the floor element 1, with the exception of the top layer 3 and the backing layer 4. The actual substrate 2 is composed of laths 6 of another material, for example, of softwood.

(91) FIGS. 31 and 32 represent other examples, wherein this time the male coupling part 9 is made of a fiber-filled synthetic material composite. FIG. 33 in its turn represents an example where the female coupling part 10 is provided on such insert 20.

(92) FIG. 32 shows the female coupling part 10 as having a projecting end part 101 formed by the substrate 2. The projecting end part 101 comprises the horizontally active locking portion 14, and the horizontally active locking portion 14 is thus also formed by the substrate 2. The horizontally active locking portion 14 comprises a horizontally active locking surface 102 which is under an angle respect to the horizontal direction H1.

(93) It is clear that in all preceding examples of separate edge portions of synthetic material or fiber-filled synthetic material composite, such edge portion may also be provided at two opposite sides, such that the male as well as the female coupling part are made at least partially or entirely

on such edge portion.

(94) In respect to all aspects of the invention, it is also noted that in the cases where a separate edge portion or insert of synthetic material forms an entire side of the respective floor element, possibly with the exception of the top layer and/or the backing layer, a water-tight protection of the actual substrate may be obtained at the side concerned. Of course, in order to obtain an entire water-tight protection, it is desirable to provide protective provisions at all edges of the respective floor element, whether or not in the form of such separate edge portion or insert.

(95) In the forms of embodiment or aspects in which a backing layer is mentioned, it is clear that such backing layer is solely optional. In particular, it may be omitted in floor elements of the type “engineered wood” in order to form a floor element, such as “dual layer parquet”.

(96) Further, it is noted that according to the invention filled synthetic material composites differ from materials such as MDF, HDF and chipboard in that they have a higher content of synthetic material. This content of synthetic material preferably is higher than 10 percent, and still better higher than 20 percent. By this high content of synthetic material, it can be obtained that the matrix of these filled synthetic materials is formed by the respective synthetic material.

(97) According to all aspects, also cavities may be provided in the synthetic material or filled synthetic composite material, by which, for example, an economization of material can be obtained and/or the mechanical features of the obtained edge portion or any other portion may be influenced.

(98) In particular, in respect to wood fiber-filled and/or wood chip-filled synthetic material composites, such as extruded wood, it is noted additionally that they also may show the following advantageous features, which can be usefully applied in flooring applications. Such materials may be resistant against splitting, deformation and/or splintering; they may be treated with the milling tools that are applied, for example, for treating MDF; these materials may be made anti-bacterial, waterproof and/or moisture-proof; they may be made in different colors, amongst which, the color of wood; when touched, they may feel like traditional wood; they may be made recyclable and/or maintenance-friendly.

(99) The present invention is in no way limited to the forms of embodiment described as an example and represented in the figures; on the contrary, such floor coverings, floor panels and methods may be realized according to various variants, without leaving the scope of the invention.

(100) It is clear that the terms “floor covering” and “floor elements” are to be understood in the broadest sense. They relate to any coverings or elements that can be applied as floor coverings or floor elements, even if they are not commercialized to this aim.

Claims

1. A floor element for forming a floor covering, comprising: a first pair of opposite sides, including first and second opposite sides, comprising a first coupling part on the first opposite side, and a second coupling part on the second opposite side, wherein the first coupling part comprises a male coupling part and the second coupling part comprises a female coupling part, and wherein the first coupling part and the second coupling part are provided with vertically active locking portions, arranged such that, the first and second coupling parts cooperate with corresponding coupling parts of another floor element and, as coupled to the another floor element, effect a locking in a vertical direction, perpendicular to a plane of the floor covering, wherein the first coupling part and the second coupling part comprise horizontally active locking portions, arranged such that the first and second coupling parts cooperate with the corresponding coupling parts of the another floor element and, as coupled to the another floor element, effect a locking in a horizontal direction, perpendicular to the first pair of opposite sides and in the plane of the floor covering, wherein the first and second coupling parts are arranged such that the floor element is configured to couple to the corresponding coupling parts of the another floor element by a horizontal shifting movement and a downward movement; wherein the floor element comprises a substrate and a top layer, and

wherein the substrate is made of a filled synthetic material composite and the first and second coupling parts are formed in the substrate, such that both of the vertically active locking portions and the horizontally active locking portions are entirely made of the filled synthetic material composite, and wherein the top layer comprises a decorative film with a printed decor; wherein the filled synthetic material composite comprises a thermoplastic material and an inorganic filling material; wherein a weight ratio between the thermoplastic material and the inorganic filling material is between 50:50 and 10:90; and wherein the first and second coupling parts are milled profiles.

2. The floor element of claim 1, wherein the thermoplastic material is selected from polyethylene, polypropylene and polyvinylchloride.

3. The floor element of claim 1, wherein floor element is rectangular and the first pair of opposite sides is located on a first pair of short sides of the floor element and a second pair of opposite sides, including third and fourth opposite sides, is located on a first pair of long sides of the floor element; and wherein the third opposite side comprises a third coupling part and the other fourth opposite side comprises a fourth coupling part; wherein the third coupling part comprises a male coupling part and the fourth coupling part comprises a female coupling part, and wherein the third coupling part and the fourth coupling part are provided with vertically active locking portions, arranged such that the third and fourth coupling parts cooperate with corresponding coupling parts of another floor element and, as coupled to the another floor element, effect a locking in a vertical direction, perpendicular to a plane of the floor covering, wherein the third coupling part and the fourth coupling part comprise horizontally active locking portions, arranged such that the third and fourth coupling parts cooperate with the corresponding coupling parts of the another floor element and, as coupled to the another floor element, effect a locking in a horizontal direction, perpendicular to the second pair of opposite sides and in the plane of the floor covering.

4. The floor element of claim 1, wherein the male coupling part for the first coupling part comprises a tongue and the female coupling part for the second coupling part comprises a groove delimited by a lower lip and an upper lip, wherein the horizontally active locking portions comprise an upright locking element on the lower lip and, interacting therewith, a downward directed locking element on an underside of the tongue.

5. The floor element of claim 4, wherein the lower lip projects beyond an upper edge at the respective side and comprises a bendable portion, and wherein the first and second coupling parts are configured to couple to the corresponding coupling parts of the another floor element by a snap-on action.

6. The floor element of claim 5, wherein the bendable portion is configured to be capable of deforming and is at least partially relaxed at an end of the snap-on action.

7. The floor element of claim 1, wherein said downward movement has a vertical component and a horizontal component.

8. A floor element for forming a floor covering, comprising: a first pair of opposite sides, including first and second opposite sides, comprising a first coupling part on the first opposite side, and a second coupling part on the the second opposite side, wherein the first coupling part comprises a male coupling part and the second coupling part comprises a female coupling part, and wherein the first coupling part and the second coupling part are provided with vertically active locking portions arranged such that the first and second coupling parts cooperate with the corresponding coupling parts of another floor element and, as coupled to the another floor element, effect a locking in a vertical direction, perpendicular to a plane of the floor covering, wherein the first coupling part and the second coupling part comprise horizontally active locking portions arranged such that the first and second coupling parts cooperate with the corresponding coupling parts of the another floor element and, as coupled to the another floor element, effect a locking in a horizontal direction, perpendicular to the first pair of opposite sides and in the plane of the floor covering, wherein the male coupling part for the first coupling part comprises a tongue and the female coupling part for

the second coupling part comprises a groove delimited by a lower lip and an upper lip, wherein the horizontally active locking portions comprise an upright locking element on the lower lip and, interacting therewith, a downward directed locking element on an underside of the tongue, wherein the first and the second coupling parts are arranged such that the floor element is configured to couple to the corresponding coupling parts of the another floor element by a downward movement, said downward movement comprising a horizontal component and a vertical component; wherein the floor element comprises a substrate and a top layer, wherein the substrate made of a filled synthetic material composite and the first and second coupling parts are formed in the substrate, such that both of the vertically active locking portions and the horizontally active locking portions are entirely made of the filled synthetic material composite, and wherein the top layer comprises a decorative film with a printed decor; wherein the filled synthetic material composite comprises a thermoplastic material and an inorganic filling material; wherein a weight ratio between the thermoplastic material and the inorganic filling material is lower than 50:50; wherein the first and second coupling parts are milled profiles; and wherein the thermoplastic material is selected from polyethylene, polypropylene and polyvinylchloride.

9. The floor element of claim 8, wherein the filled synthetic material composite has a content of thermoplastic material greater than 10 percent.

10. The floor element of claim 8, wherein the filled synthetic material composite has a content of thermoplastic material greater than 20 percent.

11. The floor element of claim 8, wherein the male coupling part for the first coupling part comprises a tongue and the female coupling part for the second coupling part comprises a groove delimited by a lower lip and an upper lip, wherein the horizontally active locking portions comprise an upright locking element on the lower lip and, interacting therewith, a downward directed locking element on an underside of the tongue.

12. The floor element of claim 11, wherein the lower lip projects beyond an upper edge at the respective side and comprises a bendable portion, and wherein the first and second coupling parts are configured to couple to the corresponding coupling parts of the another floor element by a snap-on action.

13. A floor element for forming a floor covering, comprising: a first pair of opposite sides, including first and second opposite sides, comprising a first coupling part on the first opposite side, and a second coupling part on the second opposite side, wherein the first coupling part comprises a male coupling part and the second coupling part comprises a female coupling part, and wherein the first coupling part and the second coupling part are provided with vertically active locking portions, arranged such that the first and second coupling parts cooperate with the corresponding coupling parts of another floor element and, as coupled to the another floor element, effect a locking in a vertical direction, perpendicular to a plane of the floor covering, wherein the first coupling part and the second coupling part comprise horizontally active locking portions arranged such that the first and second coupling parts cooperate with the corresponding coupling parts of the another floor element and, as coupled to the another floor element, effect a locking in a horizontal direction, perpendicular to the first pair of opposite sides and in the plane of the floor covering, wherein the male coupling part for the first coupling part comprises a tongue and the female coupling part for the second coupling part comprises a groove delimited by a lower lip and an upper lip, wherein the horizontally active locking portions comprise an upright locking element on the lower lip and, interacting therewith, a downward directed locking element on an underside of the tongue, wherein the first and second coupling parts are arranged such that the floor element is configured to couple to the corresponding coupling parts of the another floor element by a horizontal shifting movement or a downward movement; wherein the female coupling part comprises a bendable portion formed at least by a portion of the female coupling part projecting beyond an upper edge at the respective side; wherein the first and second coupling parts are arranged such that the floor element is configured to couple to the corresponding coupling parts of the another floor element by a snap-on

action; wherein the floor element comprises a substrate and a top layer, wherein the substrate made of a filled synthetic material composite and the first and second coupling parts are formed in the substrate, such that both of the vertically active locking portions and the horizontally active locking portions are entirely made of the filled synthetic material composite, and wherein the top layer comprises a decorative film with a printed decor; wherein the filled synthetic material composite comprises a thermoplastic material and an inorganic filling material; wherein a weight ratio between the thermoplastic material and the inorganic filling material is lower than 50:50; wherein the first and second coupling parts are milled profiles; and wherein the thermoplastic material is selected from polyethylene, polypropylene and polyvinylchloride.

14. The floor element of claim 13, wherein said downward movement has a vertical component and a horizontal component.

15. The floor element of claim 14, wherein the horizontal component dominates.

16. The floor element of claim 14, wherein the filled synthetic material composite has a content of thermoplastic material greater than 10 percent.

17. The floor element of claim 16, wherein the milled profiles are made with a milling process using rotating milling tools.

18. The floor element of claim 13, wherein the filled synthetic material composite has a content of thermoplastic material greater than 20 percent.

19. The floor element of claim 13, wherein the substrate comprises an upper side and an under side facing downward toward the floor, the upper side provided with the top layer, wherein the floor element comprises a backing layer on the underside, wherein the filled synthetic material composite is between the backing layer and the top layer.

20. The floor element of claim 13, wherein the filled synthetic material composite is an extruded filled synthetic material composite.
