



(12) **United States Patent**
Shen

(10) **Patent No.:** **US 12,396,226 B2**
(45) **Date of Patent:** ***Aug. 19, 2025**

(54) **SEMICONDUCTOR DEVICE HAVING NANOSHEET TRANSISTOR AND METHODS OF FABRICATION THEREOF**

(71) Applicant: **TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.**, Hsinchu (TW)

(72) Inventor: **Shu-Wen Shen**, Hsinchu (TW)

(73) Assignee: **TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.**, Hsinchu (TW)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **18/627,635**

(22) Filed: **Apr. 5, 2024**

(65) **Prior Publication Data**

US 2024/0250124 A1 Jul. 25, 2024

Related U.S. Application Data

(63) Continuation of application No. 17/993,598, filed on Nov. 23, 2022, now Pat. No. 11,961,887, which is a (Continued)

(51) **Int. Cl.**
H10D 62/10 (2025.01)
H10D 30/01 (2025.01)
(Continued)

(52) **U.S. Cl.**
CPC **H10D 62/121** (2025.01); **H10D 30/024** (2025.01); **H10D 30/031** (2025.01);
(Continued)

(58) **Field of Classification Search**
CPC H01L 29/42392; H01L 29/78696; H01L 29/0653; H01L 21/823418; H01L 29/0673;
(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

9,209,247 B2 12/2015 Colinge et al.
9,236,267 B2 1/2016 De et al.
(Continued)


Primary Examiner — Changhyun Yi

(74) *Attorney, Agent, or Firm* — NZ Carr Law Office

(57) **ABSTRACT**

A semiconductor device structure is provided. The device includes a plurality of semiconductor layers vertically stacked, and a gate electrode layer comprising an upper portion disposed between two adjacent gate spacers, the upper portion having a first diameter. The gate electrode layer also includes a lower portion disposed below the upper portion including a first part surrounding each semiconductor layer of the plurality of semiconductor layers and a second part adjacent the first part, the second part comprising a first section having a second diameter that is less than the first diameter, a second section below the first section, the second section having a third diameter different than the second diameter, and a third section below the second section, wherein the third section has a fourth diameter different than the second diameter and the third diameter, wherein the first and second parts are formed as an integral.

20 Claims, 32 Drawing Sheets



Related U.S. Application Data

continuation of application No. 17/367,559, filed on Jul. 5, 2021, now Pat. No. 11,515,393.

- (60) Provisional application No. 63/168,895, filed on Mar. 31, 2021.

29/66742; H01L 29/7851; H01L 29/66795; H01L 21/823431; H10D 30/6735; H10D 30/6757; H10D 30/024; H10D 84/013

See application file for complete search history.

(51) **Int. Cl.**

H10D 30/62 (2025.01)
H10D 30/67 (2025.01)
H10D 84/01 (2025.01)
H10D 84/03 (2025.01)

(52) **U.S. Cl.**

CPC **H10D 30/6211** (2025.01); **H10D 30/6219** (2025.01); **H10D 30/6735** (2025.01); **H10D 30/6757** (2025.01); **H10D 84/013** (2025.01); **H10D 84/0158** (2025.01); **H10D 84/038** (2025.01)

(58) **Field of Classification Search**

CPC H01L 29/41791; H01L 29/6656; H01L 29/6653; H01L 21/823481; H01L 21/823437; H01L 29/66545; H01L

(56)

References Cited

U.S. PATENT DOCUMENTS

9,412,817 B2	8/2016	Yang et al.
9,412,828 B2	8/2016	Ching et al.
9,472,618 B2	10/2016	Oxland
9,502,265 B1	11/2016	Jiang et al.
9,520,482 B1	12/2016	Chang et al.
9,536,738 B2	1/2017	Huang et al.
9,576,814 B2	2/2017	Wu et al.
9,608,116 B2	3/2017	Ching et al.
11,515,393 B2	11/2022	Shen
11,961,887 B2 *	4/2024	Shen H01L 29/1079
2020/0395445 A1	12/2020	Choi et al.
2021/0050415 A1	2/2021	Bhuwalka et al.
2021/0217860 A1	7/2021	Ha et al.

* cited by examiner

100





FIG. 1






FIG. 3








FIG. 4














FIG. 9






FIG. 10D






FIG. 10C






FIG. 11D




FIG. 11C




FIG. 12A




FIG. 12B



FIG. 12C




FIG. 12D






FIG. 12E






FIG. 13C




FIG. 14A




FIG. 14B




FIG. 14C




FIG. 15C




FIG. 16A

FIG. 16B




FIG. 16C




FIG. 17B

FIG. 17A

100




FIG. 17D

100




FIG. 17C




FIG. 18




FIG. 19B




FIG. 19A






FIG. 20C






FIG. 21C

1

SEMICONDUCTOR DEVICE HAVING NANOSHEET TRANSISTOR AND METHODS OF FABRICATION THEREOF

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation application of U.S. patent application Ser. No. 17/993,598 filed Nov. 23, 2022, which is a continuation application of U.S. patent application Ser. No. 17/367,559 filed Jul. 5, 2021, which claims a priority to a U.S. provisional application Ser. No. 63/168,895 filed on Mar. 31, 2021, which are incorporated by reference in their entirety.

BACKGROUND

The semiconductor integrated circuit (IC) industry has experienced exponential growth. Technological advances in IC materials and design have produced generations of ICs where each generation has smaller and more complex circuits than the previous generation. In the course of IC evolution, functional density (i.e., the number of interconnected devices per chip area) has generally increased while geometry size (i.e., the smallest component (or line) that can be created using a fabrication process) has decreased. This scaling down process generally provides benefits by increasing production efficiency and lowering associated costs. Such scaling down presents new challenge.

In pursuit of higher device density, higher performance, and lower costs, challenges from both fabrication and design issues have resulted in the development of three-dimensional designs, such as a multi-gate field effect transistor (FET), including a nanosheet FET. In a nanosheet FET, all side surfaces of the channel region are surrounded by the gate electrode, which allows for fuller depletion in the channel and results in less short-channel effects and better gate control. As transistor dimensions are continually scaled down, further improvements of the nanosheet FET are needed.

BRIEF DESCRIPTION OF THE DRAWINGS

Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

FIGS. 1-9 are perspective views of various stages of manufacturing a semiconductor device structure in accordance with some embodiments.

FIGS. 10A, 11A, 12A, 13A, 14A, 15A, 16A, and 17A are cross-sectional views of one of the various stages of manufacturing the semiconductor device structure taken along cross-section A-A of FIG. 9, in accordance with some embodiments.

FIGS. 10B, 11B, 12B, 13B, 14B, 15B, 16B, and 17B are cross-sectional side views of the semiconductor device structure taken along cross-section B-B of FIG. 9, in accordance with some embodiments.

FIGS. 10C, 11C, 12C, 13C, 14C, 15C, 16C, and 17C are cross-sectional views of one of the various stages of manufacturing the semiconductor device structure taken along cross-section C-C of FIG. 9, in accordance with some embodiments.

2

FIGS. 10D, 11D, and 12D are cross-sectional views of one of the various stages of manufacturing the semiconductor device structure taken along cross-section D-D of FIG. 9, in accordance with some embodiments.

FIG. 17D is an enlarged view of a portion of the semiconductor device structure of FIG. 17A, in accordance with some embodiments.

FIG. 12E is an enlarged view of a portion of the semiconductor device structure of FIG. 12D, in accordance with some embodiments.

FIG. 18 is an enlarged view of a region of FIG. 17B showing various stages of manufacturing the semiconductor device structure, in accordance with some embodiments.

FIG. 19A is a cross-sectional view of one of the various stages of manufacturing the semiconductor device structure taken along cross-section D-D of FIG. 9, in accordance with some embodiments.

FIG. 19B is an enlarged view of a portion of the semiconductor device structure of FIG. 19A, in accordance with some embodiments.

FIGS. 20A, 20B, and 20C to 21A, 21B, and 21C are cross-sectional views of one of the various stages of the semiconductor device structure taken along cross-sections A-A, B-B, and C-C of FIG. 9, in accordance with some embodiments.

DETAILED DESCRIPTION

The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “over,” “on,” “top,” “upper” and the like, may be used herein for ease of description to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

While the embodiments of this disclosure are discussed with respect to nanosheet channel FETs, implementations of some aspects of the present disclosure may be used in other processes and/or in other devices, such as planar FETs, Fin-FETs, Horizontal Gate All Around (HGAA) FETs, Vertical Gate All Around (VGAA) FETs, and other suitable devices. A person having ordinary skill in the art will readily understand other modifications that may be made are contemplated within the scope of this disclosure. In cases where gate all around (GAA) transistor structures are adapted, the GAA transistor structures may be patterned by any suitable

method. For example, the structures may be patterned using one or more photolithography processes, including double-patterning or multi-patterning processes. Generally, double-patterning or multi-patterning processes combine photolithography and self-aligned processes, allowing patterns to be created that have, for example, pitches smaller than what is otherwise obtainable using a single, direct photolithography process. For example, in one embodiment, a sacrificial layer is formed over a substrate and patterned using a photolithography process. Spacers are formed alongside the patterned sacrificial layer using a self-aligned process. The sacrificial layer is then removed, and the remaining spacers may then be used to pattern the GAA structure.

FIGS. 1-21C show exemplary processes for manufacturing a semiconductor device structure **100** according to embodiments of the present disclosure. It is understood that additional operations can be provided before, during, and after processes shown by FIGS. 1-21C, and some of the operations described below can be replaced or eliminated, for additional embodiments of the method. The order of the operations/processes is not limiting and may be interchangeable.

FIGS. 1-9 are perspective views of various stages of manufacturing a semiconductor device structure **100** in accordance with some embodiments. As shown in FIG. 1, a semiconductor device structure **100** includes a stack of semiconductor layers **104** formed over a substrate **101**. The substrate **101** may be a semiconductor substrate. The substrate **101** may include a single crystalline semiconductor material such as, but not limited to silicon (Si), germanium (Ge), silicon germanium (SiGe), gallium arsenide (GaAs), indium antimonide (InSb), gallium phosphide (GaP), gallium antimonide (GaSb), indium aluminum arsenide (InAlAs), indium gallium arsenide (InGaAs), gallium antimony phosphide (GaSbP), gallium arsenic antimonide (GaAsSb) and indium phosphide (InP). In one embodiment, the substrate **101** is made of silicon. In some embodiments, the substrate **101** is a silicon-on-insulator (an) substrate having an insulating layer (not shown) disposed between two silicon layers for enhancement. In one aspect, the insulating layer is an oxygen-containing layer.

The substrate **101** may include various regions that have been doped with impurities (e.g., dopants having p-type or n-type conductivity). Depending on circuit design, the dopants may be, for example boron for p-type field effect transistors (p-type FETs) and phosphorus for n-type field effect transistors (n-type FETs).

The stack of semiconductor layers **104** includes semiconductor layers made of different materials to facilitate formation of nanosheet channels in a multi-gate device, such as nanosheet channel FETs. In some embodiments, the stack of semiconductor layers **104** includes first semiconductor layers **106** and second semiconductor layers **108**. In some embodiments, the stack of semiconductor layers **104** includes first and second semiconductor layers **106, 108** that are alternately arranged. The first semiconductor layers **106** and the second semiconductor layers **108** are made of semiconductor materials having different etch selectivity and/or oxidation rates. For example, the first semiconductor layers **106** may be made of Si and the second semiconductor layers **108** may be made of SiGe. In some examples, the first semiconductor layers **106** may be made of SiGe and the second semiconductor layers **108** may be made of Si. Alternatively, in some embodiments, either of the semiconductor layers **106, 108** may be or include other materials

such as Ge, SiC, GeAs, GaP, InP, InAs, InSb, GaAsP, AlInAs, AlGaAs, InGaAs, GaInP, GaInAsP, or any combinations thereof.

The thickness of the first semiconductor layer **106** and the second semiconductor layer **108** may vary depending on the application and/or device performance considerations. In some embodiments, each first and second semiconductor layer **106, 108** has a thickness in a range between about 5 nm and about 30 nm. In other embodiments, each first and second semiconductor layer **106, 108** has a thickness in a range between about 10 nm and about 20 nm. In some embodiments, each first and second semiconductor layer **106, 108** has a thickness in a range between about 6 nm and about 12 nm. Each second semiconductor layer **108** may have a thickness that is equal, less, or greater than the thickness of the first semiconductor layer **106**. The second semiconductor layers **108** may eventually be removed and serve to define a vertical distance between adjacent channels for the semiconductor device structure **100**.

The first semiconductor layers **106** or portions thereof may form nanosheet channel(s) of the semiconductor device structure **100** in later fabrication stages. The term nanosheet is used herein to designate any material portion with nanoscale, or even microscale dimensions, and having an elongate shape, regardless of the cross-sectional shape of this portion. Thus, this term designates both circular and substantially circular cross-section elongate material portions, and beam or bar-shaped material portions including, for example, a cylindrical in shape or substantially rectangular cross-section. The nanosheet channel(s) of the semiconductor device structure **100** may be surrounded by a gate electrode. The semiconductor device structure **100** may include a nanosheet transistor. The nanosheet transistors may be referred to as nanowire transistors, gate-all-around (GAA) transistors, multi-bridge channel (MBC) transistors, or any transistors having the gate electrode surrounding the channels. The use of the first semiconductor layers **106** to define a channel or channels of the semiconductor device structure **100** is further discussed below.

The first and second semiconductor layers **106, 108** are formed by any suitable deposition process, such as epitaxy. By way of example, epitaxial growth of the layers of the stack of semiconductor layers **104** may be performed by a molecular beam epitaxy (MBE) process, a metalorganic chemical vapor deposition (MOCVD) process, and/or other suitable epitaxial growth processes. While three first semiconductor layers **106** and three second semiconductor layers **108** are alternately arranged as illustrated in FIG. 1, it can be appreciated that any number of first and second semiconductor layers **106, 108** can be formed in the stack of semiconductor layers **104**, depending on the predetermined number of nanosheet channels needed for each FET of the semiconductor device structure **100**. For example, the number of first semiconductor layers **106**, which is the number of channels, may be between 2 and 8.

In FIG. 2, fin structures **112** are formed from the stack of semiconductor layers **104**. Each fin structure **112** has an upper portion including the semiconductor layers **106, 108**, a well portion **116** formed from the substrate **101**, and a portion of a mask structure **110**. The mask structure **110** is formed over the stack of semiconductor layers **104** prior to forming the fin structures **112**. The mask structure **110** may include a pad layer **110a** and a hard mask **110b**. The pad layer **110a** may be an oxygen-containing layer, such as a SiO₂ layer, or a nitrogen-containing layer, such as Si₃N₄.

5

The mask structure **110** may be formed by any suitable deposition process, such as chemical vapor deposition (CVD) process.

The fin structures **112** may be fabricated using suitable processes including photolithography and etch processes. In some embodiments, the photolithography process may include forming a photoresist layer (not shown) over the mask structure **110**, exposing the resist to a pattern, performing post-exposure bake processes, and developing the resist to form a patterned resist. The patterned resist may then be used to protect regions of the substrate **101**, and layers formed thereupon, while an etch process forms trenches **114** in unprotected regions through the mask structure **110**, the stack of semiconductor layers **104**, and into the substrate **101**, thereby leaving the extending fin structures **112**. The trenches **114** may be etched using a dry etch (e.g., RIE), a wet etch, and/or combination thereof. While two fin structures **112** are shown, the number of the fin structures is not limited to two.

In FIG. 3, after the fin structures **112** are formed, an insulating material **118** is formed in the trenches **114** between the fin structures **112**. The insulating material **118** fills the trenches **114** between neighboring fin structures **112** until the fin structures **112** are embedded in the insulating material **118**. Then, a planarization operation, such as a chemical mechanical polishing (CMP) method and/or an etch-back method, is performed to expose the top of the fin structures **112**. The insulating material **118** may be made of silicon oxide, silicon nitride, silicon oxynitride (SiON), SiOCN, SiCN, fluorine-doped silicate glass (FSG), a low-K dielectric material, or any suitable dielectric material. The insulating material **118** may be formed by any suitable method, such as low-pressure chemical vapor deposition (LPCVD), plasma enhanced CVD (PECVD) or flowable CVD (FCVD).

Next, the insulating material **118** is recessed to form an isolation region **120**. The recess of the insulating material **118** exposes portions of the fin structures **112**. The isolation region **120** may be formed using a suitable process, such as a dry etching process, a wet etching process, or a combination thereof. A top surface of the insulating material **118** may be level with or below a surface of the second semiconductor layers **108** in contact with the well portion **116**.

In some embodiments, a pre-clean process may be performed to remove residues from exposed surfaces of the fin structures **112**. The pre-clean process may be any suitable wet cleaning process including, for example, hydrofluoric acid (HF), standard clean 1 (SC1), and ozonated deionized water (DIO₃). In one embodiment, the pre-clean process is performed by exposing the semiconductor device structure **100** to HF (1:500 dilution) for about 25 seconds to about 60 seconds, such as about 40 seconds, followed by the DIO 3 rinsing for about 20 seconds to about 50 seconds, such as about 30 seconds, and SC1 cleaning, which is a mixture of deionized (DI) water, ammonia hydroxide (NH₄OH), and hydrogen peroxide (H₂O₂), for about 35 seconds to about 70 seconds, such as about 50 seconds. Other pre-clean process, such as an APM process, which includes at least water (H₂O), NH₄OH, and H₂O₂, a HPM process, which includes at least H₂O, H₂O₂, and hydrogen chloride (HCl), a SPM process (also known as piranha clean), which includes at least H₂O₂ and sulfuric acid (H₂SO₄), or any combination thereof, may also be used.

In FIG. 4, a cladding (or sacrificial) layer **117** is formed by an epitaxial process over exposed portion of the fin structures **112**. In some embodiments, a semiconductor liner (not shown) may be first formed over the fin structures **112**,

6

and the cladding layer **117** is then formed over the semiconductor liner. The semiconductor liner may be diffused into the cladding layer **117** during the formation of the cladding layer **117**. In either case, the cladding layer **117** is in contact with the stack of semiconductor layers **104**. In some embodiments, the cladding layer **117** and the second semiconductor layers **108** include the same material having the same etch selectivity. For example, the cladding layer **117** and the second semiconductor layers **108** may be or include SiGe. In one embodiment, the cladding layer **117** is SiGe in amorphous state (a-SiGe). The cladding layer **117** and the second semiconductor layers **108** may be removed subsequently to create space for the gate electrode layer.

In FIG. 5, portions of the cladding layer **117** are removed to expose the mask structure **110** (e.g., hard mask **110b**) and the insulating material **118**. The removal of the portion of the cladding layer **117** may be performed by any suitable process, such as dry etch, wet etch, or a combination thereof. In some embodiments, the removal process is an anisotropic etch process which removes the cladding layer **117** on horizontal surfaces of the fin structures **112** and the insulating material **118**, while the cladding layer **117** on the sidewalls of the fin structures **112** remain substantially intact after the removal process. The thickness T1 of the cladding layer **117** formed on the sidewalls of the fin structures **112** is selected to define the space suitable for a subsequent gate electrode layer around the nanosheet channels of the nanosheet FET device. In some embodiments, the thickness T1 may be in a range between about 1 nm and about 15 nm. If the thickness T1 of the cladding layer **117** is less than 1 nm, the space created by the subsequent removal of the cladding layer **117** may be too small to form the gate electrode layer. On the other hand, if the thickness of the cladding layer **117** is greater than 15 nm, the manufacturing cost is increased without significant advantage.

In some embodiments, the removal process is performed so that only the cladding layer **117** on the insulating material **118** is removed. The cladding layer **117** on the horizontal and vertical surfaces of the fin structures **112** remain substantially intact.

In FIG. 6, a liner **119** is formed on the cladding layer **117** and the top surface of the insulating material **118**. In some embodiments, the liner **119** may include a low-k dielectric material (e.g., a material having a k value lower than 7). For example, the liner **119** may be a nitrogen-containing layer, an oxygen-containing layer, or a silicon-containing layer. Exemplary materials may include, but are not limited to, SiO₂, SiN, SiCN, SiOC, SiOCN, or the like. In one embodiment, the liner **119** is SiCN. The liner **119** may be formed by a conformal process, such as an ALD process.

The liner **119** may function as an oxidizing blocking layer that reduce the oxidation of the cladding layer **117**. The liner **119** also helps to prevent germanium loss from the cladding layer **117**. The thickness T2 of the liner **119** formed on the cladding layer **117** is selected to minimize oxidation of the cladding layer **117**. In some embodiments, the thickness T2 may be in a range between about 4 nm and about 6 nm, for example about 4.5 nm. In cases where cladding layer **117** is formed of amorphous SiGe, it has been observed that germanium loss is more susceptible than crystalline SiGe due to the presence of a great number of dangling bonds in the amorphous SiGe which has less binding energy than that of covalent bonds in the crystalline SiGe. Therefore, germanium may diffuse out of the cladding layer **117** (and becoming a low Ge % cladding layer **117**) and react with oxygen (O₂) to form germanium oxide (GeO₂). The germanium oxide may react with silicon diffused from the first

semiconductor layer **106** and/or substrate **101** during the subsequent thermal treatment (e.g., anneal process) and be reduced to germanium piling up at regions along interfaces between the fin structures **112** and the cladding layer **117**. The low Ge % cladding layer **117** and germanium piled up at regions along interfaces between the fin structures **112** and the cladding layer **117** may lead to underetching of the cladding layer **117** during recessing of the second semiconductor layers **108** and formation of the nanosheet channels. When the cladding layer **117** is underetched, a top portion of the cladding layer **117** may show a (concave shape) smiling profile which affects the profile of the dielectric spacers **144** (FIG. 12D) to be formed on the recessed cladding layer **117** in the subsequent process. Therefore, if the thickness T2 of the liner **119** is less than 4 nm, the liner **119** might not function properly to minimize the oxidation of the cladding layer **117** and prevent germanium loss from the cladding layer **117**. On the other hand, if the thickness of the liner **119** is greater than 6 nm, the manufacturing cost is increased without significant advantage.

After the liner **119** is formed, a dielectric material **121** is formed in the trenches **114** (FIG. 5) and on the liner **119**. The dielectric material **121** may be an oxygen-containing material, such as an oxide, formed by FCVD. The oxygen-containing material may have a k value less than about 7, for example less than about 3. In some embodiments, after the dielectric material **121** is deposited, an anneal process may be performed on the dielectric material **121**. Then, a second dielectric material (not shown) may be formed on the annealed dielectric material **121**. The second dielectric material may have a thickness less than the thickness of the dielectric material **121**. For example, the second dielectric material may have a thickness that is about 1/3 of the thickness of the dielectric material **121**. The second dielectric material may be formed by PECVD. A planarization process, such as a CMP process, may be performed to remove portions of the liner **119**, the second dielectric material (if used), and a portion of the dielectric material **121** formed over the fin structures **112**. The portion of the cladding layer **117** disposed on the hard mask **110b** is exposed after the planarization process.

Next, the liner **119** and the dielectric material **121** are recessed using any suitable process to the level of the topmost first semiconductor layer **106** (or slightly below). For example, in some embodiments, after the recess process, the top surfaces of the liner **119** and the dielectric material **121** may be recessed to level with a top surface of the topmost first semiconductor layer **106**. The etch processes may be selective etch processes that do not remove the semiconductor material of the cladding layer **117** and the hard mask **110b**. As a result of the recess process, trenches **123** are formed between the fin structures **112**, as shown in FIG. 6.

In FIG. 7, a dielectric material **125** is formed in the trenches **123** (FIG. 6) and on the dielectric material **121** and the liner **119**. The dielectric material **125** may include SiO, SiN, SiC, SiCN, SiON, SiOCN, AlO, AN, AlON, ZrO, ZrN, ZrAlO, HfO, or other suitable dielectric material. In some embodiments, the dielectric material **125** includes a high-k dielectric material (e.g., a material having a k value greater than 7). The dielectric material **125** may be formed by any suitable process, such as a CVD, PECVD, FCVD, or ALD process. A planarization process, such as a CMP process, is then performed until the hard mask **110b** of the mask structure **110** is exposed. The planarization process removes portions of the dielectric material **125** (and the cladding layer **117** disposed over the mask structure **110** in cases

where the cladding layer **117** on the horizontal surface of the fin structures **112** was not removed). The liner **119**, the dielectric material **121**, and the dielectric material **125** together may be referred to as a dielectric feature **127** or a hybrid fin. The dielectric feature **127** serves as a dielectric fin that separates subsequent source/drain (S/D) epitaxial features and adjacent gate electrode layers.

In some embodiments, after the planarization process to remove portions of the dielectric material **125**, the semiconductor device structure **100** is subjected to a thermal treatment. The thermal treatment may help crystallize the dielectric material **125** so that the dielectric material **125** can withstand the etchants used during subsequent removal of the sacrificial gate structure **130** (e.g., FIG. 16B). The thermal treatment may be performed in-situ or ex-situ and can be any type of anneal, such as rapid thermal anneal, a spike anneal, a soak anneal, a laser anneal, a furnace anneal, etc. The thermal treatment may be performed for about 10 seconds to about 5 minutes, such as about 20 seconds to about 90 seconds, and at a lower temperature (e.g., below 900° C.), for example in a temperature range of about 600° C. and about 850° C., such as about 680° C. to about 750° C. In one embodiment, the thermal treatment is a spike anneal performed at a temperature of about 700° C. for about 30 seconds. If the thermal treatment is performed below 600° C., the dielectric material **125** may not be crystallized and provide mechanical strength sufficient to withstand the etchants used during the removal of the sacrificial gate structure **130**. On the other hand, if the thermal treatment is performed at a temperature above 850° C. (e.g., above 900° C.), the thermal budget left for the subsequent processes is reduced which may affect performance of the devices formed after. The lower temperature will also help with germanium preservation in the cladding layer **117**, thereby improving smiling profile at the top portion of the cladding layer **117** during the subsequent removal process.

The thermal treatment may be performed in an atmosphere of gas, such as a hydrogen-containing gas, an argon-containing gas, a helium-containing gas, or any combinations thereof. Exemplary gas may include, but are not limited to, N₂, NH₃, O₂, N₂O, Ar, He, H, etc.

In FIG. 8, the cladding layers **117** are recessed, and the mask structures **110** are removed. The recess of the cladding layers **117** may be performed by any suitable process, such as dry etch, wet etch, or a combination thereof. The recess process may be controlled so that the remaining cladding layers **117** are substantially at the same level as the top surface of the topmost first semiconductor layer **106** in the stack of semiconductor layers **104**. The etch process may be a selective etch process that does not remove the dielectric material **125**. The removal of the mask structures **110** may be performed by any suitable process, such as dry etch, wet etch, or a combination thereof.

In FIG. 9, one or more sacrificial gate structures **130** (only one is shown) are formed over the semiconductor device structure **100**. The sacrificial gate structures **130** are formed over a portion of the fin structures **112**. Each sacrificial gate structure **130** may include a sacrificial gate dielectric layer **132**, a sacrificial gate electrode layer **134**, and a mask layer **136**. The sacrificial gate dielectric layer **132**, the sacrificial gate electrode layer **134**, and the mask layer **136** may be formed by sequentially depositing blanket layers of the sacrificial gate dielectric layer **132**, the sacrificial gate electrode layer **134**, and the mask layer **136**, followed by pattern and etch processes. For example, the pattern process includes a lithography process (e.g., photolithography or e-beam lithography) which may further include photoresist

coating (e.g., spin-on coating), soft baking, mask aligning, exposure, post-exposure baking, photoresist developing, rinsing, drying (e.g., spin-drying and/or hard baking), other suitable lithography techniques, and/or combinations thereof. In some embodiments, the etch process may include dry etch (e.g., RIE), wet etch, other etch methods, and/or combinations thereof.

In some embodiments, which can be combined with any one or more embodiments of this disclosure, after formation of the sacrificial gate dielectric layer **132**, the semiconductor device structure **100** is proceeded to form the sacrificial gate electrode layer **134** on the sacrificial gate dielectric layer **132** without performing an anneal process. That is, the sacrificial gate dielectric layer **132** is not subjected to an anneal process or any thermal treatment. As a result, the thermal budget for various subsequent processes is increased.

By patterning the sacrificial gate structure **130**, the stacks of semiconductor layers **104** of the fin structures **112** are partially exposed on opposite sides of the sacrificial gate structure **130**. The portions of the fin structures **112** that are covered by the sacrificial gate electrode layer **134** of the sacrificial gate structure **130** serve as channel regions for the semiconductor device structure **100**. The fin structures **112** that are partially exposed on opposite sides of the sacrificial gate structure **130** define source/drain (S/D) regions for the semiconductor device structure **100**. While one sacrificial gate structure **130** is shown, two or more sacrificial gate structures **130** may be arranged along the X direction in some embodiments.

Next, gate spacers **138** are formed on sidewalls of the sacrificial gate structures **130**. The gate spacers **138** may be formed by first depositing a conformal layer that is subsequently etched back to form gate spacers **138**. For example, a spacer material layer can be disposed conformally on the exposed surfaces of the semiconductor device structure **100**. The conformal spacer material layer may be formed by an ALD process. Subsequently, anisotropic etch is performed on the spacer material layer using, for example, RIE. During the anisotropic etch process, most of the spacer material layer is removed from horizontal surfaces, such as the tops of the fin structures **112**, the cladding layer **117**, the dielectric material **125**, leaving the gate spacers **138** on the vertical surfaces, such as the sidewalls of sacrificial gate structures **130**. The gate spacer **138** may be made of a dielectric material such as silicon oxide, silicon nitride, silicon carbide, silicon oxynitride, SiCN, silicon oxycarbide, SiOCN, and/or combinations thereof.

FIGS. **10A-17A** are cross-sectional views of one of the various stages of manufacturing the semiconductor device structure **100** taken along cross-section A-A of FIG. **9**, in accordance with some embodiments. FIGS. **10B-17B** are cross-sectional side views of the semiconductor device structure **100** taken along cross-section B-B of FIG. **9**, in accordance with some embodiments. FIGS. **10C-17C** are cross-sectional views of one of the various stages of manufacturing the semiconductor device structure **100** taken along cross-section C-C of FIG. **9**, in accordance with some embodiments. FIGS. **10D-12D** are cross-sectional views of one of the various stages of manufacturing the semiconductor device structure **100** taken along cross-section D-D of FIG. **9**, in accordance with some embodiments. Cross-section A-A is in a plane of the fin structure **112** along the X direction. Cross-section B-B is in a plane perpendicular to cross-section A-A and is in the sacrificial gate structure **130**. Cross-section C-C is in a plane perpendicular to cross-section A-A and is in the epitaxial S/D features **146** (FIG.

13C) along the Y-direction. Cross-section D-D is in a plane of the cladding layer **117** along the X direction.

In FIGS. **10A-10D**, exposed portions of the fin structures **112**, exposed portions of the cladding layers **117**, and exposed portions of the dielectric material **125** not covered by the sacrificial gate structures **130** and the gate spacers **138** are selectively recessed by using one or more suitable etch processes, such as dry etch, wet etch, or a combination thereof. In some embodiments, exposed portions of the stacks of semiconductor layers **104** of the fin structures **112** are removed, exposing portions of the well portions **116**. As shown in FIG. **10A**, the exposed portions of the fin structures **112** are recessed to a level at or slightly below the bottom surface of the second semiconductor layer **108** in contact with the well portion **116** of the substrate **101**. The recess processes may include an etch process that recesses the exposed portions of the fin structures **112** and the exposed portions of the cladding layers **117**.

In FIGS. **11A-11D**, edge portions of each second semiconductor layer **108** of the stack of semiconductor layers **104** are removed horizontally along the X direction. The removal of the edge portions of the second semiconductor layers **108** forms cavities **141**. In some embodiments, the portions of the second semiconductor layers **108** are removed by a selective wet etching process. In cases where the second semiconductor layers **108** are made of SiGe and the first semiconductor layers **106** are made of silicon, the second semiconductor layer **108** can be selectively etched using a wet etchant such as, but not limited to, ammonium hydroxide (NH₄OH), tetramethylammonium hydroxide (TMAH), ethylenediamine pyrocatechol (EDP), or potassium hydroxide (KOH) solutions.

During the recess etching of the second semiconductor layer **108**, end portions of the cladding layer **117** are also horizontally etched along the X direction. In some embodiments, the etched amount of the cladding layer **117** is greater than the recessed amount of the second semiconductor layers **108**. Since the thickness "T2" of the liner **119** is controlled to minimize germanium loss from the cladding layer **117**, the underetch of the cladding layer **117** during the recess etching is minimized, resulting in the cladding layer **117** with different profiles at the top portion **117t** and the bottom portion **117b** of the cladding layer **117**. For example, the etching of the end portions of the cladding layer **117** may form curved cavities **135** in the X-Z plane of the semiconductor device structure **100**. The curved cavities **135** are substantially symmetric with respect to a longitudinal axis of the sacrificial gate structure **130**. Stated differently, the top portion **117t** of the cladding layer **117** may have a curved surface having a first radius (Re) of curvature **137** and the bottom portion **117b** of the cladding layer **117** may have a curved surface having a second radius (Re) of curvature **139** that is greater than the first radius (Re) of curvature **137**. In some embodiments, the ratio of the first radius (Re) of curvature **137** to the second radius (Re) of curvature **139** may be in the range of about 0.5 to about 0.9, for example about 0.6 to about 0.8. While not wishing to be bound by any particular theory, the difference between the first and second radius (Re) of curvatures **137**, **139** may be partly due to the top portion **117t** being exposed to a greater amount of the etchant during the etch process than that of the bottom portion **117b**. As will be discussed in more detail below, the radius (Re) of curvatures of the top and bottom portions **117t**, **117b** affect the profile of the dielectric spacers **144** (FIG. **12E**) to be formed in the curved cavities **135** of the cladding layer **117**.

11

In FIGS. 12A-12D, after removing edge portions of each second semiconductor layers 108, a dielectric layer is deposited in the cavities 141 (FIG. 11A) formed in the edge portions of the second semiconductor layers 108 and the recessed, curved cavities 135 (FIG. 11D) of the cladding layer 117 to form dielectric spacers 144. The dielectric spacers 144 may be made of a low-k dielectric material, such as SiON, SiCN, SiOC, SiOCN, or SiN. The dielectric spacers 144 may be formed by first forming a conformal dielectric layer using a conformal deposition process, such as ALD, followed by an anisotropic etching to remove portions of the conformal dielectric layer other than the dielectric spacers 144. Portions of the dielectric spacers 144 are protected by the first semiconductor layers 106 during the anisotropic etching process. The remaining second semiconductor layers 108 are capped between the dielectric spacers 144 along the X direction.

The dielectric spacers 144 in contact with the cladding layer 117 are formed in accordance with the profile of the curved cavity 135 formed in the cladding layer 117. In some embodiments, each dielectric spacer 144 is formed to have a first side 143a that is under and substantially flush with the gate spacers 138, and a second side 143b that is opposite the first side 143a. The first side 143a has a substantially flat surface. The second side 143b is shaped in accordance with the profile of the top and bottom portions 117t, 117b of the cladding layer 117. The term “being substantially flush” herein means the difference in the relative position is less than about 1 nm. FIG. 12E is an enlarged view of a portion of the semiconductor device structure 100 of FIG. 12D, showing the positional relationship between the dielectric spacer 144 and the layers adjacent the dielectric spacer 144, in accordance with some embodiments. In FIG. 12E, the second side 143b of the dielectric spacer 144 includes an upper section 143b-1 adjacent the gate spacers 138 and in contact with the first semiconductor layer 106 (e.g., first semiconductor layer 106a represented by dotted lines), and a lower section 143b-3 adjacent the insulating material 118 and in contact with the first semiconductor layer 106 (e.g., first semiconductor layer 106c represented by dotted lines). The second side 143b of the dielectric spacer 144 also includes a middle section 143b-2 between the upper section 143b-1 and the lower section 143b-3 of the second side 143b. The middle section 143b-2 is substantially flat. In some embodiments, the upper section of the second side 143b has a first radius (R_0) of curvature 145t and the lower section of the second side 143b has a second radius (R_0) of curvature 145b greater than the first radius (R_0) of curvature 145t. The first radius (R_0) of curvature 145t corresponds to the first radius (R_0) of curvature 137 of the top portion 117t of the cladding layer 117 (FIG. 11D), and the second radius (R_0) of curvature 145b corresponding to the second radius (R_0) of curvature 139 of the bottom portion 117b of the cladding layer 117 (FIG. 11D).

In FIGS. 13A-13C, epitaxial S/D features 146 are formed on the well portion 116 of the fin structures 112. The epitaxial S/D feature 146 may include one or more layers of Si, SiP, SiC and SiCP for an n-type FET or Si, SiGe, Ge for a p-type FET. The epitaxial S/D features 146 may grow both vertically and horizontally to form facets, which may correspond to crystalline planes of the material used for the substrate 101. The epitaxial S/D features 146 are formed by an epitaxial growth method using CVD, ALD or MBE. The epitaxial S/D features 146 are in contact with the first semiconductor layers 106 and dielectric spacers 144. The epitaxial S/D features 146 may be the S/D regions. For example, one of a pair of epitaxial S/D features 146 located

12

on one side of the sacrificial gate structures 130 can be a source region, and the other of the pair of epitaxial S/D features 146 located on the other side of the sacrificial gate structures 130 can be a drain region. A pair of epitaxial S/D features 146 includes a source epitaxial feature 146 and a drain epitaxial feature 146 connected by the channels (i.e., the first semiconductor layers 106). In this disclosure, a source and a drain are interchangeably used, and the structures thereof are substantially the same.

In FIGS. 14A-14C, after formation of the epitaxial S/D features 146, a contact etch stop layer (CESL) 162 is conformally formed on the exposed surfaces of the semiconductor device structure 100. The CESL 162 covers the epitaxial S/D features 146, the gate spacers 138, the dielectric material 125, and the exposed surface of the stack of semiconductor layers 104. The CESL 162 may include an oxygen-containing material or a nitrogen-containing material, such as silicon nitride, silicon carbon nitride, silicon oxynitride, carbon nitride, silicon oxide, silicon carbon oxide, or the like, or a combination thereof, and may be formed by CVD, PECVD, ALD, or any suitable deposition technique. Next, an interlayer dielectric (ILD) layer 164 is formed on the CESL 162 over the semiconductor device structure 100. The materials for the ILD layer 164 may include tetraethylorthosilicate (TEOS) oxide, un-doped silicate glass, or doped silicon oxide such as borophosphosilicate glass (BPSG), fused silica glass (FSG), phosphosilicate glass (PSG), boron doped silicon glass (BSG), and/or other suitable dielectric materials comprising Si, O, C, and/or H. The ILD layer 164 may be deposited by a PECVD process or other suitable deposition technique. In some embodiments, after formation of the ILD layer 164, the semiconductor device structure 100 may be subject to a thermal process to anneal the ILD layer 164.

In FIGS. 15A-15C, after the ILD layer 164 is formed, a planarization operation, such as CMP, is performed on the semiconductor device structure 100 to remove portions of the ILD layer 164, the CESL 162 and the mask layer 136 until the sacrificial gate electrode layer 134 is exposed.

In FIGS. 16A-16C, the sacrificial gate structure 130 is removed. The removal of the sacrificial gate structure 130 forms a trench 166 in the regions where the sacrificial gate electrode layer 134 and the sacrificial gate dielectric layer 132 were removed. The trench 166 exposes portions of the cladding layer 117 and the top of the first semiconductor layer 106. The ILD layer 164 protects the epitaxial S/D features 146 during the removal of the sacrificial gate structure 130. The sacrificial gate structure 130 can be removed using plasma dry etching and/or wet etching. The sacrificial gate electrode layer 134 may be first removed by any suitable process, such as dry etch, wet etch, or a combination thereof, followed by the removal of the sacrificial gate dielectric layer 132, which may also be performed by any suitable process, such as dry etch, wet etch, or a combination thereof. In some embodiments, a wet etchant such as a tetramethylammonium hydroxide (TMAH) solution can be used to selectively remove the sacrificial gate electrode layer 134 but not the gate spacers 138, the dielectric material 125, and the CESL 162. In some embodiments, the gate spacers 138 may be recessed by the etchant used to remove the sacrificial gate electrode layer 134 and/or the sacrificial gate dielectric layer 132.

In FIGS. 17A-17C, the cladding layers 117 and the second semiconductor layers 108 are removed. The removal of the cladding layers 117 and the second semiconductor layers 108 exposes the dielectric spacers 144 and the first semiconductor layers 106. The removal process may be any

13

suitable etch processes, such as dry etch, wet etch, or a combination thereof. The etch process may be a selective etch process that removes the cladding layers **117** (FIG. **14B**) and the second semiconductor layers **108** but not the gate spacers **138**, the CESL **162**, the dielectric material **125**, and the first semiconductor layers **106**. As a result, openings **151** are formed around the first semiconductor layers **106**, and the portion of the first semiconductor layers **106** not covered by the dielectric spacers **144** is exposed to the openings **151**. FIG. **17D** further illustrates the dielectric spacers **144** being exposed to the openings **151** in accordance with some embodiments.

FIG. **18** is an enlarged view of a region **147** of FIG. **17B** showing various stages of manufacturing the semiconductor device structure **100** in accordance with some embodiments. In FIG. **18**, an interfacial layer (IL) **178** is formed to surround surfaces of the first semiconductor layers **106**. The IL **178** may also form on the exposed surfaces of the well portion **116** of the substrate **101**. The IL **178** may include or be made of an oxygen-containing material or a silicon-containing material, such as silicon oxide, silicon oxynitride, oxynitride, hafnium silicate, etc. In some embodiments, the IL **178** is formed by CVD, ALD or any suitable conformal deposition technique. In some embodiments, the IL **178** is formed by subjecting the first semiconductor layers **106** and well portion **116** of the substrate **101** to a wet cleaning process to oxidize a surface portion of the first semiconductor layers **106**.

Next, a high-k (HK) dielectric layer **180** is formed on the exposed surfaces of the semiconductor device structure **100**. In some embodiments, the HK dielectric layer **180** is formed on the IL **178**, a portion of the insulating material **118**, and on the exposed surfaces of the dielectric feature **127** (e.g., the liner **119** and the dielectric material **125**), as shown in FIG. **18**. As will be discussed in further details, portions of the HK dielectric layer **180** are also in contact with the dielectric spacers **144**.

Suitable materials for the HK dielectric layer **180** may include, but are not limited to, SiN, SiON, SiCN, SiOCN, AlSi_xO_y, Al₂O₃, or the like. Other suitable high-k materials, such as hafnium oxide (HfO₂), hafnium silicate (HfSiO), hafnium silicon oxynitride (HfSiON), hafnium aluminum oxide (HfAlO), hafnium lanthanum oxide (HfLaO), hafnium zirconium oxide (HfZrO), hafnium tantalum oxide (HfTaO), hafnium titanium oxide (HfTiO), lanthanum oxide (LaO), zirconium oxide (ZrO), zirconium silicon oxide (ZrSiO), titanium oxide (TiO), tantalum oxide (Ta₂O₅), yttrium oxide (Y₂O₃), may also be used. The HK dielectric layer **180** may be formed by any suitable process, such as a CVD, PECVD, FCVD, or ALD process.

After formation of the IL **178** and the HK dielectric layer **180**, a gate electrode layer **182** is formed in the openings **151** (FIG. **17B**). The gate electrode layer **182** is formed on the HK dielectric layer **180** to surround a portion of each first semiconductor layer **106** and on the HK dielectric layer **180** that is in contact with the dielectric feature **127** and the insulating material **118**. The gate electrode layer **182** may include one or more layers of conductive material, such as polysilicon, aluminum, copper, titanium, tantalum, tungsten, cobalt, molybdenum, tantalum nitride, nickel silicide, cobalt silicide, TiN, WN, TiAl, TiAlN, TaCN, TaC, TaSiN, metal alloys, other suitable materials, and/or combinations thereof. The gate electrode layer **182** may be formed by PVD, CVD, ALD, electro-plating, or other suitable method. The gate electrode layer **182** is formed to a predetermined height above the dielectric feature **127**, as shown in FIG. **18**.

14

FIG. **19A** is a cross-sectional view of one of the various stages of manufacturing the semiconductor device structure **100** taken along cross-section D-D of FIG. **9**, in accordance with some embodiments. As can be seen in FIG. **19A**, the gate electrode layer **182** generally includes a first part **182a** and a second part **182b** below the first part **182a**. The first part **182a** of the gate electrode layer **182** is in contact with the HK dielectric layer **180** between the gate spacers **138**. In some embodiments, the first part **182a** has a generally uniform cross-section along the longitudinal direction of the gate electrode layer **182**. The second part **182b** is in contact with the HK dielectric layer **180** between the dielectric spacers **144**. The second part **182b** is shaped in accordance with the profile of the dielectric spacers **144**, such as the profile discussed above with respect to FIG. **12E**.

FIG. **19B** is an enlarged view of a portion of the semiconductor device structure **100** of FIG. **19A**, showing the positional relationship between the second part **182b** of the gate electrode layer **182** and the layers adjacent to the gate electrode layer **182**, in accordance with some embodiments. In FIG. **19B**, the second part **182b** of the gate electrode layer **182** includes an upper portion **182b-1** adjacent one of the first semiconductor layers **106** (e.g., first semiconductor layer **106a** represented by dotted lines), a middle portion **182b-2** adjacent one of the first semiconductor layers **106** (e.g., first semiconductor layer **106b** represented by dotted lines), and a bottom portion **182b-3** adjacent one of the first semiconductor layers **106** (e.g., first semiconductor layer **106c** represented by dotted lines). The upper portion **182b-1** may have a first dimension D1, the middle portion **182b-2** may have a second dimension D2, and the bottom portion **182b-3** may have a third dimension D3. In some embodiments, the first dimension D1 is greater than the second dimension D2, and the third dimension D3 is greater than the first dimension D1. In some embodiments, which can be combined with any other embodiment of the present disclosure, the upper portion **182b-1** has a curved exterior surface having a first radius (R₀) of curvature **187**, the middle portion **182b-2** has a substantially flat surface **189**, and the bottom portion **182b-3** has a curved exterior surface having a second radius (R₀) of curvature **191** that is greater than the first radius (R₀) of curvature **187**. In some embodiments, the first radius (R₀) of curvature **187** substantially corresponds to the first radius (R₀) of curvature **145a** (of the upper section of the second side **143b** of the dielectric spacers **144**), and the second radius (R₀) of curvature **191** substantially corresponds to the second radius (R₀) of curvature **145b** (of the lower section of the second side **143b** of the dielectric spacers **144**). In one embodiment, the ratio of the first radius (R₀) of curvature **187** to the second radius (R₀) of curvature **191** may be in the range of about 0.5 to about 0.9, for example about 0.6 to about 0.8.

FIGS. **20A-20C** to **21A-21C** are cross-sectional views of one of the various stages of the semiconductor device structure **100** taken along cross-sections A-A, B-B, and C-C of FIG. **9**, in accordance with some embodiments. FIGS. **20A-20C** show the semiconductor device structure **100** after formation of the gate electrode layer **182**.

In FIGS. **21A-21C**, one or more metal gate etching back (MGE) processes are performed so that top surfaces of the gate electrode layer **182** and the HK dielectric layer **180** are substantially co-planar. The MGE processes may be any suitable process, such as a dry etch, a wet etch, or a combination thereof. In some embodiments, portions of the spacers **138** may be etched back so that the top surface of the spacers **138** is higher than the top surfaces of the gate electrode layer **182** and the HK dielectric layer **180**. In such

15

cases, trenches formed above the gate electrode layer **182** and the HK dielectric layer **180** as a result of the MGBE processes may be filled with a self-aligned contact (SAC) layer **173**. The SAC layer **173** can be formed of any dielectric material that has different etch selectivity than the CESL **162** and serves as an etch stop layer during subsequent trench and via patterning for metal contacts.

After formation of the self-aligned contact layer **173**, contact openings are formed through the ILD layer **164** (FIG. **19A**) and the CESL **162** to expose the epitaxial S/D feature **146**. A silicide layer **181** is then formed on the epitaxial S/D features **146** to conductively couple the epitaxial S/D features **146** to the subsequently formed S/D contacts **176**. The silicide layer **181** may be formed by depositing a metal source layer over the epitaxial S/D features **146** and performing a rapid thermal annealing process. The metal source layer includes a metal layer selected from W, Co, Ni, Ti, Mo, and Ta, or a metal nitride layer selected from tungsten nitride, cobalt nitride, nickel nitride, titanium nitride, molybdenum nitride, and tantalum nitride. During the rapid anneal process, the portion of the metal source layer over the epitaxial S/D features **146** reacts with silicon in the epitaxial S/D features **146** to form the silicide layer **181**. Unreacted portion of the metal source layer is then removed.

After formation of the silicide layer **181**, a conductive material is formed in the contact openings and form the S/D contacts **176**. The conductive material may be made of a material including one or more of Ru, Mo, Co, Ni, W, Ti, Ta, Cu, Al, TiN and TaN. While not shown, a barrier layer (e.g., TiN, TaN, or the like) may be formed on sidewalls of the contact openings prior to forming the S/D contacts **176**. Once the S/D contacts **176** are formed, a planarization process, such as CMP, is performed to expose the top surface of the SAC layer **173** (or top surface of the gate electrode layer **182** if the SAC layer **173** was not used).

It is understood that the semiconductor device structure **100** may undergo further complementary metal oxide semiconductor (CMOS) and/or back-end-of-line (BEOL) processes to form various features such as transistors, contacts/vias, interconnect metal layers, dielectric layers, passivation layers, etc. The semiconductor device structure **100** may also include backside contacts (not shown) on the backside of the substrate **101** by flipping over the semiconductor device structure **100**, removing the substrate **101**, and selectively connecting source or drain feature/terminal of the epitaxial S/D features **146** to a backside power rail (e.g., positive voltage VDD or negative voltage VSS) through the backside contacts. Depending on the application, the source or drain feature/terminal of the epitaxial S/D features **146** and the gate electrode layer **182** may be connected to a frontside power source.

Various embodiments or examples described herein offer multiple advantages over the state-of-art technology. According to embodiments of the present disclosure, methods for preventing germanium loss from cladding layer during fabrication of semiconductor device structures are provided. Germanium loss from cladding layer may lead to underetching of the cladding layer during formation of nanosheet channels in gate all around (GAA) transistors, such as nanosheet FETs. In some embodiments, the method includes forming fin structures each having first semiconductor layer (e.g., Si) and second semiconductor layer (e.g., SiGe) alternately arranged, forming a germanium-containing cladding layer on the fin structures, and forming a conformal nitrogen-containing layer on the cladding layer. The nitrogen-containing layer may function as an oxidizing

16

blocking layer that reduce the oxidation of the cladding layer. The method further includes forming a high-k dielectric layer on a hybrid fin structure disposed between the fin structures, annealing the high-k dielectric layer at a reduced temperature range between about 600° C. and about 850° C., which helps with germanium preservation in the cladding layer, thereby improving smiling profile at top portion of the cladding layer during the subsequent removal process. As thermal budget reduction and oxidizing blocking layer together prevent germanium loss in the cladding layer, underetching of the cladding layer during recessing of the second semiconductor layers and formation of the nanosheet channels can be avoided.

An embodiment is a semiconductor device structure. The device includes a plurality of semiconductor layers vertically stacked, and a gate electrode layer comprising an upper portion disposed between two adjacent gate spacers, the upper portion having a first diameter. The gate electrode layer also includes a lower portion disposed below the upper portion including a first part surrounding each semiconductor layer of the plurality of semiconductor layers and a second part adjacent the first part, the second part comprising a first section having a second diameter that is less than the first diameter, a second section below the first section, the second section having a third diameter different than the second diameter, and a third section below the second section, wherein the third section has a fourth diameter different than the second diameter and the third diameter, wherein the first and second parts are formed as an integral.

Another embodiment is a semiconductor device structure. The structure includes a plurality of semiconductor layers vertically stacked, a gate electrode layer surrounding each semiconductor layer of the plurality of semiconductor layers, a dielectric spacer disposed adjacent to the gate electrode layer, and a high-k (HK) dielectric layer having a first surface in contact with the gate electrode layer and a second surface in contact with the dielectric spacer. The HK dielectric layer comprises a first section having a curved surface, a second section having a curved surface, and a third section between the first and second sections, the third section has a substantially flat surface.

A further embodiment is a method for forming a semiconductor device structure. The method includes forming a fin structure comprising a plurality of first semiconductor layers and a plurality of second semiconductor layers alternately stacked, forming a sacrificial layer on exposed sidewall surfaces of the fin structure, forming a sacrificial gate structure over a portion of the fin structure and the sacrificial layer, removing portions of the fin structure and the sacrificial layer not covered by the sacrificial gate structure, removing edge portions of the sacrificial layer and edge portions of each of the plurality of second semiconductor layers in the fin structure so that edge portions of the sacrificial layer are etched at an amount different than that of edge portions of each of the plurality of second semiconductor layers. The method also includes forming a dielectric spacer in cavities formed as a result of removal of the edge portions of the sacrificial layer and edge portions of each of the plurality of second semiconductor layers, forming an epitaxial source/drain feature on opposite sides of the sacrificial gate structure, the source/drain feature being in contact with the dielectric spacer and each of the plurality of first semiconductor layers in the fin structure. The method further includes removing the sacrificial layer and the second semiconductor layers to expose portions of each of the plurality of first semiconductor layers, and forming a gate

17

electrode layer to surround each of the plurality of first semiconductor layers of fin structure.

The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

The invention claimed is:

1. A semiconductor device structure, comprising:
a plurality of semiconductor layers vertically stacked; and
a gate electrode layer comprising:
an upper portion disposed between two adjacent gate spacers, the upper portion having a first diameter;
a lower portion disposed below the upper portion, comprising:
a first part surrounding each semiconductor layer of the plurality of semiconductor layers; and
a second part adjacent the first part, comprising:
a first section having a second diameter that is less than the first diameter;
a second section below the first section, the second section having a third diameter different than the second diameter; and
a third section below the second section, wherein the third section has a fourth diameter different than the second diameter and the third diameter, wherein the first and second parts are formed as an integral.
2. The semiconductor device structure of claim 1, wherein the third diameter is less than the second diameter.
3. The semiconductor device structure of claim 2, wherein the fourth diameter is greater than the second diameter.
4. The semiconductor device structure of claim 1, wherein the second section has a substantially flat surface.
5. The semiconductor device structure of claim 1, wherein the first section has a first radius of curvature and the third section has a second radius of curvature different than the first radius of curvature.
6. The semiconductor device structure of claim 1, wherein the lower portion extends across the plurality of semiconductor layers.
7. The semiconductor device structure of claim 1, wherein the first section is at an elevation above an interface defined by a source/drain feature and a contact etch stop layer (CESL), and the second section is at an elevation below the interface.
8. The semiconductor device structure of claim 5, further comprising:
a high-k (HK) dielectric layer in contact with the gate electrode layer and surrounding each semiconductor layer of the plurality of semiconductor layers; and
dielectric spacers in contact with the HK dielectric layer, wherein the second part is disposed between two adjacent dielectric spacers.
9. A semiconductor device structure, comprising:
a plurality of semiconductor layers vertically stacked;
a gate electrode layer surrounding each semiconductor layer of the plurality of semiconductor layers;

18

a dielectric spacer disposed adjacent to the gate electrode layer; and

a high-k (HK) dielectric layer having a first surface in contact with the gate electrode layer and a second surface in contact with the dielectric spacer, wherein the HK dielectric layer comprises:

a first section having a curved surface;

a second section having a curved surface; and

a third section between the first and second sections, the third section has a substantially flat surface.

10. The semiconductor device structure of claim 9, wherein the first section has a first radius of curvature and the second section has a second radius of curvature different than the first radius of curvature.

11. The semiconductor device structure of claim 10, wherein the second radius of curvature is greater than the first radius of curvature.

12. The semiconductor device structure of claim 9, wherein the dielectric spacer is in contact with each semiconductor layer of the plurality of semiconductor layers.

13. The semiconductor device structure of claim 12, wherein the HK dielectric layer is in contact with each semiconductor layer of the plurality of semiconductor layers.

14. The semiconductor device structure of claim 13, wherein the first section is in contact with a topmost semiconductor layer of the plurality of semiconductor layers.

15. The semiconductor device structure of claim 13, wherein the third section is in contact with a bottommost semiconductor layer of the plurality of semiconductor layers.

16. The semiconductor device structure of claim 9, wherein the gate electrode layer

a first portion having a first dimension;

a second portion having a second dimension greater than the first dimension; and

a third portion disposed between the first and second portions, wherein the third portion has a third dimension less than the first dimension.

17. A method for forming a semiconductor device structure, comprising:

forming a fin structure comprising a plurality of first semiconductor layers and a plurality of second semiconductor layers alternately stacked;

forming a sacrificial layer on exposed sidewall surfaces of the fin structure;

forming a sacrificial gate structure over a portion of the fin structure and the sacrificial layer;

removing portions of the fin structure and the sacrificial layer not covered by the sacrificial gate structure;

removing edge portions of the sacrificial layer and edge portions of each of the plurality of second semiconductor layers in the fin structure so that edge portions of the sacrificial layer are etched at an amount different than an amount of edge portions of each of the plurality of second semiconductor layers;

forming a dielectric spacer in cavities formed as a result of removal of the edge portions of the sacrificial layer and edge portions of each of the plurality of second semiconductor layers;

forming an epitaxial source/drain feature on opposite sides of the sacrificial gate structure, the source/drain feature being in contact with the dielectric spacer and each of the plurality of first semiconductor layers in the fin structure;

19

removing the sacrificial layer and the second semiconductor layers to expose portions of each of the plurality of first semiconductor layers; and

forming a gate electrode layer to surround each of the plurality of first semiconductor layers of fin structure. 5

18. The method of claim **17**, wherein the gate electrode layer has a first portion between two adjacent gate spacers and a second portion between the dielectric spacers, wherein the first portion has a first diameter and the second portion has a second diameter less than the first diameter. 10

19. The method of claim **18**, wherein the first portion has a substantially flat sidewall surface and the second portion has a curved sidewall surface.

20. The method of claim **17**, wherein the sacrificial layer is a germanium-containing layer. 15

* * * * *

20