

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250266379

Kind Code

A1

Publication Date

August 21, 2025

Inventor(s)

Chuang; Harry-Hak-Lay et al.

SLOTTED BOND PAD IN STACKED WAFER STRUCTURE

Abstract

The present disclosure relates integrated chip structure. The integrated chip structure includes one or more interconnects disposed within a dielectric structure over a substrate. A bond pad having a top surface is arranged along a top surface of the dielectric structure. The top surface of the bond pad includes a plurality of discrete top surface segments that are laterally separated from one another by non-zero distances that extend between interior sidewalls of the bond pad, as viewed in a cross-sectional view. The dielectric structure is disposed directly between the interior sidewalls of the bond pad.

Inventors: Chuang; Harry-Hak-Lay (Zhubei City, TW), Teng; Li-Feng (Hsinchu City, TW), Wu; Wei Cheng (Zhubei City, TW)

Applicant: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Family ID: 1000008576648

Appl. No.: 19/199600

Filed: May 06, 2025

Related U.S. Application Data

parent US division 17750706 20220523 parent-grant-document US 12322715 child US 19199600
us-provisional-application US 63304114 20220128

Publication Classification

Int. Cl.: H01L23/00 (20060101); H01L23/522 (20060101); H01L23/528 (20060101)

U.S. Cl.:

CPC H01L24/05 (20130101); H01L24/03 (20130101); H01L24/08 (20130101); H01L24/80 (20130101); H01L23/5226 (20130101); H01L23/5283 (20130101); H01L2224/03614

(20130101); H01L2224/03622 (20130101); H01L2224/03845 (20130101); H01L2224/05007 (20130101); H01L2224/05014 (20130101); H01L2224/05016 (20130101); H01L2224/05082 (20130101); H01L2224/05547 (20130101); H01L2224/05551 (20130101); H01L2224/05554 (20130101); H01L2224/05557 (20130101); H01L2224/05647 (20130101); H01L2224/08147 (20130101); H01L2224/80895 (20130101); H01L2224/80896 (20130101)

Background/Summary

REFERENCE TO RELATED APPLICATIONS [0001] This Application is a Divisional of U.S. application Ser. No. 17/750,706, filed on May 23, 2022, which claims the benefit of U.S. Provisional Application No. 63/304,114, filed on Jan. 28, 2022. The contents of the above-referenced Patent Applications are hereby incorporated by reference in their entirety.

BACKGROUND

[0002] A multi-dimensional integrated chip is an integrated circuit having multiple substrates and/or dies, which are vertically stacked onto and electrically interconnected to one another. By electrically interconnecting the stacked substrates and/or dies, the multi-dimensional integrated chip acts as a single device, which provides improved performance, reduced power consumption, and a reduced footprint over conventional integrated chips. Therefore, multi-dimensional integrated chips provide a path to continue to meet the performance/cost demands of next-generation integrated circuits.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0003] Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

[0004] FIGS. 1A-1B illustrate some embodiments of an integrated chip structure comprising a bond pad having one or more cavities configured to reduce dishing of the bond pad.

[0005] FIG. 2 illustrates a cross-sectional view of some embodiments of a multi-dimensional integrated chip structure comprising bond pads respectively having one or more cavities.

[0006] FIGS. 3A-3B illustrate some additional embodiments of an integrated chip structure comprising a bond pad having one or more cavities.

[0007] FIGS. 4A-4B illustrate some additional embodiments of an integrated chip structure comprising a bond pad having one or more cavities.

[0008] FIG. 5 illustrates a cross-sectional view of some embodiments of a multi-dimensional integrated chip structure comprising bond pads respectively having one or more cavities.

[0009] FIGS. 6A-6B illustrate some additional embodiments of an integrated chip structure comprising a bond pad having one or more cavities.

[0010] FIGS. 7A-7C illustrate top-views of some additional embodiments of an integrated chip structure comprising a disclosed bond pad having one or more cavities with different shapes and/or spatial configurations.

[0011] FIGS. 8A-8C illustrate some additional embodiments of an integrated chip structure comprising a bond pad having one or more cavities.

[0012] FIGS. 9A-9C illustrate top-views of some additional embodiments of an integrated chip structure comprising a disclosed bond pad having one or more cavities with different shapes and/or

spatial configurations.

[0013] FIGS. **10A-10C** illustrate some additional embodiments of an integrated chip structure comprising a disclosed bond pad having one or more cavities.

[0014] FIGS. **11-18** illustrate some embodiments of a method of forming an integrated chip structure comprising a disclosed bond pad having one or more cavities configured to reduce dishing of the bond pad.

[0015] FIGS. **19-28** illustrate some additional embodiments of a method of forming an integrated chip structure comprising a disclosed bond pad having one or more cavities configured to reduce dishing of the bond pad.

[0016] FIGS. **29-35** illustrate some additional embodiments of a method of forming an integrated chip structure comprising a disclosed bond pad having one or more cavities configured to reduce dishing of the bond pad.

[0017] FIG. **36** illustrates a flow diagram of some embodiments of a method of forming an integrated chip structure comprising a disclosed bond pad having one or more cavities configured to reduce dishing of the bond pad.

DETAILED DESCRIPTION

[0018] The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

[0019] Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

[0020] Multi-dimensional integrated chip structures (e.g., chip-on-wafer (CoW) structures, wafer-on-wafer (WoW) structures, three-dimensional integrated chip (3DIC) structures, or the like) are formed by stacking a plurality of integrated chip dies onto one another. The plurality of integrated chip dies are separately produced by forming interconnects within ILD layers overlying one or more semiconductor substrates. One or more bond pads are then formed over a top of the interconnects. The one or more bond pads may be formed by depositing a conductive material (e.g., a metal such as copper) within a bond pad opening, which extends through a dielectric material over the ILD layers, followed by a planarization process (e.g., a chemical mechanical planarization process). The bond pads of the integrated chip dies are then brought together to electrically couple the integrated chip dies.

[0021] When the planarization process is performed on the conductive material (e.g., copper) of the one or more bond pads, a polishing pad is brought into contact with both the conductive material and the surrounding dielectric material. Because the conductive material is softer than the surrounding dielectric material, the polishing pad will remove the conductive material at a faster rate than the surrounding dielectric thereby causing the conductive material to recess or ‘dish’. Such dishing causes the one or more bond pads to have a concave upper surface that drops below a

top of the surrounding dielectric material. When the bond pads of two integrated chip die are subsequently brought together, a void (e.g., spaces) may form between the concave upper surfaces of the bond pads. The void can lead to a poor electrical connection between the integrated chip dies, which can decrease performance of and/or ultimately lead to failure of a multi-dimensional integrated chip structure.

[0022] The present disclosure relates to an integrated chip structure having a bond pad that is configured to mitigate dishing along a top of the bond pad. The disclosed integrated chip structure comprises a bond pad disposed within a dielectric structure over a substrate. The bond pad comprises interior sidewalls defining one or more cavities that are surrounded by the bond pad. The one or more cavities are filled with a dielectric material of the dielectric structure, so that a top surface of the bond pad comprises a plurality of discrete top surface segments that are laterally separated from one another by the dielectric structure, as viewed in a cross-sectional view. Because the dielectric material is disposed directly between the plurality of discrete top surface segments, a polishing pad used to form the bond pad will have a relatively small overlap with individual ones of the top surface segments. The relatively small overlap reduces dishing of the individual top surface segments. The reduced dishing decreases formation of voids when bond pads of separate integrated chip die are brought together, thereby improving an electrical performance and/or a reliability of a multi-dimensional integrated chip structure.

[0023] FIG. 1A illustrates a cross-sectional view of some embodiments of an integrated chip structure **100** comprising a bond pad having one or more cavities configured to reduce dishing of the bond pad.

[0024] The integrated chip structure **100** comprises one or more interconnects **106** disposed within a dielectric structure **104** over a substrate **102**. A bond pad **112** is disposed within the dielectric structure **104** over the one or more interconnects **106**. The bond pad **112** comprises a top surface disposed along a top surface of the dielectric structure **104**. In some embodiments, the top surface of the bond pad **112** is substantially co-planar with the top surface of the dielectric structure **104**. The plurality of interconnects **106** comprise a topmost interconnect **108** disposed within the dielectric structure **104**. The topmost interconnect **108** comprises an upper surface **108u** that directly contacts a bottommost surface of the bond pad **112**. In some embodiments, the upper surface **108u** may continuously extend past outermost sidewalls of the bottom surface of the bond pad **112**.

[0025] In some embodiments, the bond pad **112** comprises a lower segment **114** and an upper segment **116** over the lower segment **114**. The lower segment **114** laterally extends between opposing outermost edges of lower sidewalls of the bond pad **112**. The lower sidewalls are arranged along a bottom of the bond pad **112**. The upper segment **116** laterally extends between opposing outermost edges of upper sidewalls of the bond pad **112**. The upper sidewalls are arranged along a top of the bond pad **112**. In some embodiments, the upper segment **116** comprises a bottom surface that laterally extends from directly over the lower segment **114** to laterally past one or more of the lower sidewalls.

[0026] The bond pad **112** further comprises one or more interior sidewalls **112s** that define one or more cavities **113** (e.g., one or more slots) within a top surface of the bond pad **112**. The one or more cavities **113** separate the top surface of the bond pad **112** into a plurality of discrete top surface segments **112u**, as viewed along the cross-sectional view of FIG. 1A. The dielectric structure **104** is disposed within the one or more cavities **113** and directly between the plurality of discrete top surface segments **112u**. In some embodiments, the bottommost surface of the bond pad **112** laterally and continuously extends past one or more of the interior sidewalls **112s** defining the one or more cavities **113**.

[0027] Because the dielectric structure **104** is disposed directly between the plurality of discrete top surface segments **112u**, an overlap between individual ones of the plurality of discrete top surface segments **112u** and a chemical mechanical polishing (CMP) pad used to form the bond pad **112** is

smaller than that of a bond pad not having one or more cavities. The smaller overlap reduces a dishing of the individual ones of the plurality of discrete top surface segments **112u**. The reduced dishing mitigates formation of voids when the bond pad **112** is brought into contact with another bond pad, thereby improving an electrical performance and/or a reliability of a multi-dimensional integrated chip structure.

[0028] FIG. **1B** illustrates a top-view **118** of some embodiments of the integrated chip structure **100** of FIG. **1A** taken along cross-sectional line A-A'. In some embodiments, the cross-sectional view of FIG. **1A** may be taken along cross-sectional line B-B' of the top-view **118**.

[0029] As shown in the top-view **118**, the bond pad **112** is surrounded by the dielectric structure **104**. The upper segment **116** of the bond pad **112** extends around the one or more cavities **113** (e.g., one or more slots), which are filled with the dielectric structure **104**. In some embodiments, the upper segment **116** continuously extends between outermost sidewalls of the bond pad **112** along a first direction **120** and/or along a second direction **122** that is perpendicular to the first direction **120**. In some embodiments, the upper segment **116** continuously wraps around the one or more cavities **113** in a closed and unbroken loop. The upper segment **116** is directly over a part of the lower segment **114**. In some embodiments, the one or more cavities **113** may also be directly over a part of the lower segment **114**.

[0030] FIG. **2** illustrates a cross-sectional view of some embodiments of a multi-dimensional integrated chip structure **200** comprising bond pads having one or more cavities.

[0031] The multi-dimensional integrated chip structure **200** comprises a first integrated chip (IC) die **202** having a plurality of interconnects **106** arranged within a dielectric structure **104** on a substrate **102**. In some embodiments, the plurality of interconnects **106** comprise a topmost interconnect **108** contacting a bond pad **112** arranged within the dielectric structure **104**. In some embodiments, the plurality of interconnects **106** may electrically couple a bond pad **112** to one or more semiconductor devices **204** on and/or within the substrate **102**. In various embodiments, the one or more semiconductor devices **204** may comprise a transistor device (e.g., a planar FET, a FinFET, a gate-all-around (GAA) device, etc.), an image sensor device (e.g., a photodiode), a MEMS (microelectromechanical system) device, and/or the like. The bond pad **112** has a top surface facing away from the substrate **102**. The top surface of the bond pad **112** is disposed along a top surface of the dielectric structure **104** facing away from the substrate **102**. The top surface comprises a plurality of discrete top surface segments that are separated by one or more cavities **113** filled with the dielectric structure **104**, as viewed in the cross-sectional view.

[0032] The multi-dimensional integrated chip structure **200** further comprises a second IC die **208** having a plurality of additional interconnects **214** arranged within an additional dielectric structure **210** on an additional substrate **212**. In some embodiments, the one or more additional interconnects **214** comprise an additional topmost interconnect **216** contacting an additional bond pad **218** arranged within the additional dielectric structure **210**. In some embodiments, the plurality of additional interconnects **214** may electrically couple an additional bond pad **218** to one or more additional semiconductor devices **222** (e.g., a transistor device, an image sensor device, a MEMS device, and/or the like) on and/or within the additional substrate **212**. The additional bond pad **218** has a surface facing away from the additional substrate **212**. The surface of the additional bond pad **218** is disposed along a surface of the additional dielectric structure **210** facing away from the additional substrate **212**. The surface of the additional bond pad **218** comprises a plurality of discrete segments that are separated by one or more additional cavities **220** filled with the additional dielectric structure **210**, as viewed in the cross-sectional view.

[0033] In some embodiments, one or more dummy bond pads **206** may be arranged along the top surface of the dielectric structure **104** facing away from the substrate **102**. The one or more dummy bond pads **206** may have a same layout as the bond pad **112**. For example, the one or more dummy bond pads **206** may have a top surface that faces away from the substrate **102** and that comprises a plurality of discrete top surface segments that are separated by one or more cavities filled with the

dielectric structure **104**, as viewed in the cross-sectional view. In some embodiments, one or more additional dummy bond pads **224** may be arranged along the surface of the additional dielectric structure **210** facing away from the additional substrate **212**. The one or more additional dummy bond pads **224** may have a same layout as the additional bond pad **218**.

[0034] The first IC die **202** is bonded to the second IC die **208** along a hybrid bonding interface, in which the bond pad **112** contacts the additional bond pad **218** along a conductive interface and the dielectric structure **104** contacts the additional dielectric structure **210** along a dielectric interface. In some embodiments, the dielectric structure **104** within the one or more cavities **113** contacts the additional dielectric structure **210** within the one or more additional cavities **220** along the dielectric interface. In some embodiments, the plurality of discrete top surface segments of the bond pad **112** may laterally overlap the plurality of discrete segments of the surface of the additional bond pad **218**. In some embodiments, at least one sidewall of the additional bond pad **218** may be directly over the top surface of the bond pad **112**.

[0035] Because the dielectric structure **104** is disposed directly between the plurality of discrete top surface segments of the bond pad **112**, the top surface of the bond pad **112** is substantially planar. Similarly, because the additional dielectric structure **210** is disposed directly between the plurality of discrete segments of the additional bond pad **218**, the surface of the additional bond pad **218** is substantially planar. The substantially planar top surface of the bond pad **112** and the substantially planar surface of the additional bond pad **218** mitigate voids along an interface between the bond pad **112** and the additional bond pad **218**, thereby improving an electrical performance and/or a reliability of the multi-dimensional integrated chip structure **200**.

[0036] FIG. 3A illustrates a cross-sectional view of some additional embodiments of an integrated chip structure comprising a disclosed bond pad having one or more cavities.

[0037] The integrated chip structure **300** comprises a dielectric structure **104** over a substrate **102**. In some embodiments, the dielectric structure **104** comprises a plurality of inter-level dielectric (ILD) layers **104a-104d** stacked onto one another. The plurality of ILD layers **104a-104d** may be vertically separated from one another by way of a plurality of etch stop layers **105a-105c**. A top dielectric layer **105t** is arranged along a top of the dielectric structure **104**. In some embodiments, the plurality of ILD layers **104a-104d** may comprise one or more of silicon dioxide, carbon doped silicon dioxide, silicon oxynitride, borosilicate glass (BSG), phosphoric silicate glass (PSG), borophosphosilicate glass (BPSG), fluorinated silicate glass (FSG), a porous dielectric material, or the like. In some embodiments, the plurality of etch stop layers **105a-105c** and/or the top dielectric layer **105t** may comprise a nitride (e.g., silicon nitride, silicon oxy-nitride, etc.), a carbide (e.g., silicon carbide, silicon oxy-carbide, etc.), or the like.

[0038] A plurality of interconnects **106** are disposed within a lower dielectric structure **104L** of the dielectric structure **104**. In some embodiments, the plurality of interconnects **106** comprise conductive contacts, interconnect wires, interconnect vias, and/or the like. The plurality of interconnects **106** comprise a topmost interconnect **108**. In some embodiments, the topmost interconnect **108** may comprise a conductive core **108c** surrounded by a barrier layer **108b**. In some embodiments, the conductive core **108c** may comprise copper, aluminum, or the like. In some embodiments, the barrier layer **108b** may comprise titanium, titanium nitride, tantalum, tantalum nitride, or the like.

[0039] A bond pad **112** is disposed within the dielectric structure **104** and contacts the topmost interconnect **108**. The bond pad **112** comprises a top surface arranged along a top surface of the dielectric structure **104**. In some embodiments, the bond pad **112** comprises a lower segment **114** and an upper segment **116** over the lower segment **114**. The lower segment **114** extends laterally between opposing outermost edges of lower sidewalls coupled to one or more bottom surfaces of the bond pad **112**. In some embodiments, the lower segment **114** may have a first width **302** that is in a range of between approximately 0.2 μm (microns) and approximately 3 μm , between approximately 0.4 μm and approximately 2 μm , or other similar values. The upper segment **116**

laterally extends between opposing outermost edges of upper outermost sidewalls of the bond pad **112**. In some embodiments, the upper segment **116** may have a second width **304** that is greater than approximately 1.5 μm , greater than approximately 2 μm , or other similar values. Typically, a bond pad with a top surface having a relatively large size (e.g., greater than approximately 1.5 μm) will experience significant dishing that can lead to the formation of voids. However, by having one or more cavities **113** within the upper segment **116** of the bond pad **112** filled with the dielectric structure **104**, the bond pad **112** is able to have a relatively large size (e.g., greater than approximately 1.5 μm) that provides for an electrical connection with another IC while avoiding significant dishing.

[0040] A lower surface of the upper segment **116** physically contacts an upper surface of the lower segment **114**. In some embodiments, the lower segment **114** may comprise a first barrier layer **114b** surrounding a first conductive core **114c**. In some embodiments, the upper segment **116** may comprise a second barrier layer **116b** surrounding a second conductive core **116c**. In some embodiments, the second barrier layer **116b** may be disposed directly between the second conductive core **116c** and the first conductive core **114c**. In some embodiments, the first conductive core **114c** and the second conductive core **116c** may comprise copper, aluminum, tungsten, or the like. In some embodiments, the first barrier layer **114b** and the second barrier layer **116b** may comprise titanium, titanium nitride, tantalum, tantalum nitride, or the like.

[0041] In some embodiments, the second barrier layer **116b** of the upper segment **116** may extend a non-zero distance below a top of the first barrier layer **114b** and/or the first conductive core **114c**. In some embodiments, the first conductive core **114c** may extend along sidewalls of the second barrier layer **116b**. In some such embodiment, the upper outermost sidewalls of the bond pad **112** may extend vertically below a top of the lower sidewalls of the bond pad **112**.

[0042] The top surface of the bond pad **112** comprises a plurality of discrete top surface segments **112u** that are laterally separated from one another by one or more cavities **113** that are defined by interior sidewalls **112s** of the bond pad **112**. In some embodiments, the upper segment **116** may also comprise discrete lower surfaces that are separated from one another by the one or more cavities **113**, as viewed in the cross-sectional view. In some embodiments, the discrete lower surfaces may respectively have a third width **306** that is in a range of between approximately 0.2 μm (microns) and approximately 3 μm , between approximately 0.4 μm and approximately 2 μm , or other similar values. The dielectric structure **104** is disposed directly between the interior sidewalls **112s** of the bond pad **112**.

[0043] FIG. 3B illustrates a top-view **308** of some embodiments of the integrated chip structure **300** of FIG. 3A taken along cross-sectional line A-A'. In some embodiments, the cross-sectional view of FIG. 3A may be taken along cross-sectional line B-B' of the top-view **308**.

[0044] As shown in the top-view **308**, the bond pad **112** is surrounded by the dielectric structure **104**. The upper segment **116** of the bond pad **112** extends around a boundary of the lower segment **114**. In some embodiments, the one or more cavities **113** extend through the upper segment **116** and directly overlie a part of the lower segment **114**. In some embodiments, the one or more cavities **113** may be rectangular shaped cavities that are surrounded by a continuous ring of the upper segment **116**. In some embodiments, the continuous ring of the upper segment **116** extends along an outer perimeter of the upper segment **116**.

[0045] FIG. 4A illustrates a cross-sectional view of some additional embodiments of an integrated chip structure **400** comprising a disclosed bond pad having one or more cavities.

[0046] The integrated chip structure **400** comprises a bond pad **112** disposed within a dielectric structure **104** over a substrate **102**. The bond pad **112** comprises a lower segment **114** and an upper segment **116** over the lower segment **114**. The lower segment **114** extends laterally between opposing outermost sidewalls that are coupled to a bottom of the bond pad **112**. The upper segment **116** extends laterally between opposing outermost sidewalls that are coupled to a top of the bond pad **112**. In some embodiments, the upper segment **116** comprises interior sidewalls **112s** that are

coupled to horizontally extending surfaces **112h** facing away from the substrate **102** to form one or more cavities **113** within a top surface of the bond pad **112**. The horizontally extending surfaces **112h** are directly above a bottom surface **117** of the upper segment **116**.

[0047] In some embodiments, the one or more cavities **113** have a depth that is less than a height of the upper segment **116**, so that the upper segment **116** extends along a bottom of the one or more cavities **113**. In some embodiments, the bottom surface **117** of the upper segment **116** laterally and continuously extends past opposing outermost sidewalls of the lower segment **114** and past the one or more cavities **113**. In some embodiments, the bottom surface **117** completely covers a top surface of the lower segment **114**.

[0048] FIG. **4B** illustrates a top-view **402** of some embodiments of the integrated chip structure **400** of FIG. **4A** taken along cross-sectional line A-A'. In some embodiments, the cross-sectional view of FIG. **4A** may be taken along cross-sectional line B-B' of the top-view **402**.

[0049] As shown in the top-view **402**, the bond pad **112** is surrounded by the dielectric structure **104**. The upper segment **116** of the bond pad **112** extends around a boundary of the lower segment **114**. In some embodiments, the one or more cavities **113** extend through the upper segment **116** and directly overlie the lower segment **114**.

[0050] FIG. **5** illustrates a cross-sectional view of some additional embodiments of a multi-dimensional integrated chip structure **500** comprising disclosed bond pads respectively having one or more cavities.

[0051] The multi-dimensional integrated chip structure **500** comprises a first IC die **202** having a bond pad **112** arranged within a dielectric structure **104** over a substrate **102**. The bond pad **112** has a top surface facing away from the substrate **102**. The top surface comprises a plurality of discrete top surface segments that are separated by one or more cavities **113** that are defined by sidewalls and a horizontally extending surface of the bond pad **112**. The one or more cavities **113** are filled with the dielectric structure **104**.

[0052] The multi-dimensional integrated chip structure **500** further comprises a second IC die **208** having an additional bond pad **218** arranged within an additional dielectric structure **210** on an additional substrate **212**. The additional bond pad **218** has a surface facing away from the additional substrate **212**. The surface comprises a plurality of discrete segments that are separated by one or more additional cavities **220** that are defined by sidewalls and a horizontally extending surface of the additional bond pad **218**. The one or more additional cavities **220** are filled with the additional dielectric structure **210**.

[0053] In some embodiments, one or more dummy bond pads **206** may be arranged along a top surface of the dielectric structure **104** facing away from the substrate **102**. The one or more dummy bond pad **206** may have a same layout as the bond pad **112**. In some embodiments, one or more additional dummy bond pads **224** may be arranged along a surface of the additional dielectric structure **210** facing away from the additional substrate **212**. The one or more additional dummy bond pad **224** may have a same layout as the additional bond pad **218**.

[0054] The first IC die **202** is bonded to the second IC die **208** along a hybrid bonding interface, in which the bond pad **112** contacts the additional bond pad **218** along a conductive interface and the dielectric structure **104** contacts the additional dielectric structure **210** along a dielectric interface (e.g., the dielectric structure **104** within the one or more cavities **113** contacts the additional dielectric structure **210** within the one or more additional cavities **220** along the dielectric interface). In some embodiments, the plurality of discrete top surface segments of the bond pad **112** and/or the plurality of discrete segments of the additional bond pad **218** may have slight dishing, which causes small voids **502** to form along the conductive interface. However, because the one or more cavities mitigate CMP dishing, the small voids **502** have a minimal impact on a performance of the multi-dimensional integrated chip structure **500**. In some embodiments, the small voids **502** may laterally extend along a part, but not all, of the conductive interface (e.g., the small voids **502** may be set back from opposing sides of the plurality of discrete top surface segments of the bond

pad **112** by non-zero distances).

[0055] Although the disclosed multi-dimensional integrated chip structures (e.g., multi-dimensional integrated chip structure **200** and/or **500**) are illustrated as three-dimensional integrated chip (3DIC) structures, it will be appreciated that the disclosed bond pad is not limited to such structures but rather may be integrated within various multi-dimensional integrated chip architectures. For example, in alternative embodiments the disclosed bond pad may be integrated within chip-on-wafer (CoW) structures, wafer-on-wafer (WoW) structures, or the like.

[0056] FIG. **6A** illustrates a cross-sectional view of some additional embodiments of an integrated chip structure **600** comprising a disclosed bond pad having one or more cavities.

[0057] The integrated chip structure **600** comprises one or more interconnects **106** disposed within a dielectric structure **104** over a substrate **102**. In some embodiments, the dielectric structure **104** comprises a plurality of inter-level dielectric (ILD) layers **104a-104e** stacked onto one another. The plurality of ILD layers **104a-104e** may be vertically separated from one another by way of a plurality of etch stop layers **105a-105d**. A top dielectric layer **105t** is arranged along a top of the dielectric structure **104**.

[0058] A bond pad **112** is disposed within the dielectric structure **104**. The bond pad **112** contacts a topmost interconnect **108** of the plurality of interconnects **106**. The bond pad **112** comprises a lower segment **114** and an upper segment **116** over the lower segment **114**. The lower segment **114** extends laterally between opposing outer sidewalls coupled to a bottom of the bond pad **112**. The upper segment **116** laterally extends between opposing outermost sidewalls of the bond pad **112**. In some embodiments, the lower segment **114** may comprise a first barrier layer **114b** surrounding a first conductive core **114c**. In some embodiments, the upper segment **116** may comprise a part of the first barrier layer **114b** surrounding a part of the first conductive core **114c** and a second barrier layer **116b** surrounding a second conductive core **116c**. In some embodiments, the second barrier layer **116b** may be disposed directly between the second conductive core **116c** and the first conductive core **114c**. In some embodiments, the second barrier layer **116b** may contact the first conductive core **114c** at a location that is above a bottom of the upper segment **116** (e.g., that is above a bottom of the opposing outermost sidewalls of the bond pad **112**). In some embodiments, the second barrier layer **116b** may extend a non-zero distance below a top of the first barrier layer **114b** and/or the first conductive core **114c**.

[0059] In some embodiments, one or more cavities **113** extend into the upper segment **116** of the bond pad **112**. The one or more cavities may be defined by sidewalls of the second barrier layer **116b** and by an upper surface of the first conductive core **114c**. The one or more cavities have a height that is less than a height of the upper segment **116** (e.g., less than heights of the opposing outermost sidewalls of the bond pad **112**).

[0060] FIG. **6B** illustrates a top-view **602** of some embodiments of the integrated chip structure **600** of FIG. **6A** taken along cross-sectional line A-A'. In some embodiments, the cross-sectional view of FIG. **6A** may be taken along cross-sectional line B-B' of the top-view **602**.

[0061] As shown in the top-view **602**, the upper segment **116** of the bond pad **112** is surrounded by the dielectric structure **104** and extends around a boundary of the lower segment **114**. In some embodiments, the one or more cavities **113** extend through the upper segment **116** and directly overlie a part of the lower segment **114**. In some embodiments, the one or more cavities **113** may be rectangular shaped regions that are surrounded by a continuous ring of the upper segment **116**. In some embodiments, the one or more cavities **113** may directly overlie a part of the lower segment **114**.

[0062] It will be appreciated that in various embodiments, an upper segment of the disclosed bond pad may have interior sidewalls defining one or more cavities having different shapes and/or spatial configurations. FIGS. **7A-7C** illustrate top-views of various embodiments of an integrated chip structure comprising a disclosed bond pad having one or more cavities with different shapes and/or spatial configurations.

[0063] FIG. 7A illustrates a top-view **700** of some embodiments of an integrated chip structure comprising a bond pad **112** having one or more cavities **113** respectively having a square shape. The square shaped cavities extend to a first distance **702** along a first direction **120** and to a second distance **704** along a second direction **122** that is perpendicular to the first direction **120**. The first distance **702** is approximately equal to the second distance **704**. The square shaped cavities are surrounded by a continuous outer ring of an upper segment **116** of the bond pad **112** that wraps around the square shaped cavities. In some embodiments, the upper segment **116** of the bond pad **112** comprises a cross-shaped region that is coupled to the outer ring of the upper segment **116**. The cross-shaped region separates the one or more cavities **113** from one another along the first direction **120** and along the second direction **122**. The square shaped cavities and the cross-shaped region are directly over a lower segment **114** of the bond pad **112**. The outer ring of the upper segment **116** is laterally outside of the lower segment **114** of the bond pad **112**.

[0064] FIG. 7B illustrates a top-view **706** of some embodiments of an integrated chip structure comprising a bond pad **112** having one or more cavities **113** respectively having a cross-shape. The cross-shaped cavity is surrounded by discrete parts of an upper segment **116** of the bond pad **112**. The discrete parts of the upper segment **116** of the bond pad **112** are directly over a lower segment **114** of the bond pad **112**. The cross-shaped cavity has branches that completely separate the discrete parts of the upper segment **116** from one another along a first direction **120** and along a second direction **122** that is perpendicular to the first direction **120**.

[0065] FIG. 7C illustrates a top-view **708** of some embodiments of an integrated chip structure comprising a bond pad **112** having one or more cavities **113** respectively having a square shape. The square shaped cavities are surrounded by a continuous outer ring of an upper segment **116** of the bond pad **112** that wraps around the square shaped cavities. The square shaped cavities directly overlie square shaped cavities extending through a lower segment **114** of the bond pad **112**. In some embodiments, the lower segment of the bond pad **112** has a same pattern as the upper segment **116** of the bond pad **112**.

[0066] FIG. 8A illustrates a top-view of some additional embodiments of an integrated chip structure **800** comprising a disclosed bond pad having one or more cavities.

[0067] The integrated chip structure **800** comprises a bond pad **112** arranged within a dielectric structure **104**. The bond pad comprises a lower segment **114** and an upper segment **116** over the lower segment **114**. The upper segment **116** comprises interior sidewalls that define one or more cavities **113** surrounded by a continuous ring of the bond pad **112**. The one or more cavities **113** are filled with the dielectric structure **104**.

[0068] The lower segment **114** may comprise a plurality of discrete lower segments **114d** that are arranged in an array. The plurality of discrete lower segments **114d** may be separated by a first distance **802** along a first direction **120** and by a second distance **804** along a second direction **122** that is perpendicular to the first direction **120**. In some embodiments, the plurality of discrete lower segments **114d** may comprise square shaped segments. In other embodiments (not shown), the plurality of discrete lower segments **114d** may comprise other shapes (e.g., circular shaped segments, octagonal shaped segments, polygonal shaped segments, or the like). In some embodiments, the plurality of discrete lower segments **114d** are completely covered by the upper segment **116**.

[0069] FIG. 8B illustrates a cross-sectional view **806** of some additional embodiments of the integrated chip structure of FIG. 8A taken along line A-A'.

[0070] As shown in cross-sectional view **806**, the one or more cavities **113** extend completely through the bond pad **112**, so that a part of the dielectric structure **104** that is between one or more sidewalls of the bond pad **112** continuously extends from a top of the bond pad **112** to a bottom of the bond pad **112**. In some embodiments, the part of the dielectric structure **104** that is between one or more sidewalls of the bond pad **112** continuously extends from the top of the bond pad **112** to a topmost interconnect **108** within the dielectric structure **104**.

[0071] The lower segment **114** of the bond pad **112** laterally extends in the first direction **120** between opposing outer edges of lower sidewalls of the bond pad **112**. The lower sidewalls are arranged along a bottom of the bond pad **112**. In some embodiments, the plurality of discrete lower segments **114d** comprise a plurality of discrete lower surfaces contacting the topmost interconnect **108** and a plurality of discrete upper surfaces contacting the upper segment **116**. Both the plurality of discrete lower surfaces and the plurality of discrete upper surfaces of the plurality of discrete lower segments **114d** are laterally separated from one another by the dielectric structure **104** in the first direction **120**.

[0072] The upper segment **116** of the bond pad **112** laterally extends between outermost sidewalls of the bond pad **112**. The outermost sidewalls are arranged along a top of the bond pad **112**. In some embodiments, the upper segment **116** may comprise a plurality of discrete lower surfaces laterally separated from one another by the dielectric structure **104**. In some embodiments, the plurality of discrete lower surfaces of the upper segment **116** may respectively have a greater width than respective ones of the plurality of discrete upper surfaces of the plurality of discrete lower segments **114d**. In some embodiments, the plurality of discrete lower surfaces of the upper segment **116** may respectively extend past one or more outer edges of the plurality of discrete upper surfaces of the plurality of discrete lower segments **114d**.

[0073] FIG. **8C** illustrates a cross-sectional view **808** of some additional embodiments of the integrated chip structure of FIG. **8A** taken along line B-B'.

[0074] As shown in cross-sectional view **808**, the plurality of discrete lower segments **114d** within the lower segment **114** are separated from one another along the second direction **122**. The upper segment **116** has a lower surface that continuously extends in the second direction **122** over the plurality of discrete lower segments **114d**.

[0075] It will be appreciated that in various embodiments, a lower segment of the disclosed bond pad may have a plurality of discrete lower segments with different shapes and/or spatial configurations. FIGS. **9A-9C** illustrate top-views of some additional embodiments of an integrated chip structure comprising a disclosed bond pad having one or more cavities.

[0076] FIG. **9A** illustrates a top-view **900** of an integrated chip structure comprising a bond pad **112** having a lower segment **114** and an upper segment **116**. The lower segment **114** comprises a plurality of discrete lower segments **114d** that are arranged in an array extending in a first direction **120** and a second direction **122**. The upper segment **116** directly overlies plurality of discrete lower segments **114d** within the array. The upper segment **116** comprises sidewalls defining one or more cavities **113** having rectangular shapes. The rectangular shaped cavities extend to a first distance **902** along a first direction **120** and to a second distance **904** along a second direction **122**. The second distance **904** is smaller than the first distance **902**. The rectangular shaped cavities are surrounded by a continuous outer ring of the upper segment **116** to separate the rectangular shaped cavities.

[0077] FIG. **9B** illustrates a top-view **906** of an integrated chip structure comprising a bond pad **112** having a lower segment **114** and an upper segment **116**. The lower segment **114** comprises a plurality of discrete lower segments **114d** that are arranged in an array extending in a first direction **120** and a second direction **122**. The upper segment **116** directly overlies the plurality of discrete lower segments **114d** within the array. The upper segment **116** comprises sidewalls defining one or more cavities **113** respectively having a square shape. The square shaped cavities are surrounded by a continuous outer ring of the upper segment **116**. A cross-shaped region of the upper segment **116** is surrounded by the continuous outer ring and separates the square shaped cavities along a first direction **120** and along a second direction **122**. The cross-shaped region comprises a first cross-bar extending in the first direction **120** and a second cross-bar extending in the second direction **122**.

[0078] FIG. **9C** illustrates a top-view **908** of an integrated chip structure comprising a bond pad **112** having a lower segment **114** and an upper segment **116**. The lower segment **114** comprises a plurality of discrete lower segments **114d** that are arranged in an array extending in a first direction

120 and a second direction **122**. The upper segment **116** comprises a plurality of discrete upper segments **116d** that are arranged in an array extending in the first direction **120** and the second direction **122**. In some embodiments, the plurality of discrete lower segments **114d** may have a smaller size than the plurality of discrete upper segments **116d**. In some such embodiments, the plurality of discrete upper segments **116d** may completely cover the plurality of discrete lower segments **114d**.

[0079] FIG. **10A** illustrates a top-view of some additional embodiments of an integrated chip structure **1000** comprising a disclosed bond pad having one or more cavities.

[0080] The integrated chip structure **1000** comprises a bond pad **112** arranged within a dielectric structure **104**. The bond pad **112** comprises a lower segment **114** and an upper segment **116** over the lower segment **114**. The lower segment **114** and the upper segment **116** respectively comprise interior sidewalls defining one or more cavities **113** that are filled with the dielectric structure **104**. In some embodiments, the one or more cavities **113** respectively have a rectangular shape. The lower segment **114** and the upper segment **116** continuously extend in a closed loop around the one or more cavities **113**. In some embodiments, the lower segment **114** is completely covered by the upper segment **116**. In some such embodiments, the interior sidewalls of the lower segment **114** are separated by a larger distance along the first direction and along the second direction than the interior sidewalls of the upper segment **116**.

[0081] In some embodiments, the upper segment **116** comprises an upper outer ring segment surrounding the one or more cavities **113** and an upper cross-bar extending between parts of the upper outer ring segment. The lower segment **114** continuously extends in a closed loop around the one or more cavities **113**. In some embodiments, the lower segment **114** comprises a lower outer ring segment surrounding the one or more cavities and a lower cross-bar extending between parts of the lower outer ring segment. The upper outer ring segment is directly over the lower outer ring segment and the upper cross-bar is directly over the lower cross-bar. The one or more cavities **113** are filled with the dielectric structure **104**.

[0082] FIG. **10B** illustrates a cross-sectional view **1002** of some additional embodiments of the integrated chip structure **1000** of FIG. **10A** taken along line A-A'.

[0083] As shown in cross-sectional view **1002**, the bond pad **112** comprises a lower segment **114** having discrete upper surfaces and an upper segment **116** having discrete lower surfaces. The plurality of discrete upper surfaces and the plurality of discrete lower surfaces are separated from one another by the dielectric structure **104** along the first direction **120**.

[0084] FIG. **10C** illustrates a cross-sectional view **1004** of some additional embodiments of the integrated chip structure of FIG. **10A** taken along line B-B'.

[0085] As shown in cross-sectional view **1004**, the bond pad **112** comprises a lower segment **114** having a lower surface and an upper surface that respectively extend between outer edges of lower sidewalls coupled to the lower surface. The bond pad **112** further comprises an upper segment **116** having a lower surface and an upper surface that respectively extend between outer edges of upper sidewalls coupled to the top surface. In some embodiments, the lower surface of the upper segment **116** continuously extends past opposing sides of the upper surface of the lower segment **114**.

[0086] FIGS. **11-18** illustrate some embodiments of a method of forming an integrated chip structure comprising a disclosed bond pad having one or more cavities configured to reduce dishing of the bond pad. Although FIGS. **11-18** are described in relation to a method, it will be appreciated that the structures disclosed in FIGS. **11-18** are not limited to such a method, but instead may stand alone as structures independent of the method.

[0087] As shown in cross-sectional view **1100** of FIG. **11**, a substrate **102** is provided. In various embodiments, the substrate **102** may be any type of semiconductor body (e.g., silicon, SiGe, SOI, etc.), such as a semiconductor wafer and/or one or more die on a wafer, as well as any other type of semiconductor and/or epitaxial layers, associated therewith. In some embodiments (not shown), one or more semiconductor devices are formed on and/or within the substrate **102**. In various

embodiments, the one or more semiconductor devices may comprise a transistor device, an image sensor device, a MEMS device, and/or the like.

[0088] One or more interconnects **106** are formed within a lower dielectric structure **104L** formed over the substrate **102**. The lower dielectric structure **104L** may comprise one or more lower inter-level dielectric (ILD) layers **104a-104b** separated by one or more etch stop layers **105a**. In some embodiments, the one or more interconnects **106** may comprise a topmost interconnect **108** comprising a barrier layer **108b** and a conductive core **108c**. In some embodiments, the topmost interconnect **108** may be formed using a damascene process (e.g., a single damascene process or a dual damascene process). The damascene process is performed by forming an ILD layer on the substrate **102**, etching the ILD layer to form a via hole and/or a trench, filling the via hole and/or the trench with a barrier layer and with a conductive material, and performing a planarization process (e.g., a CMP process). In some embodiments, the lower dielectric structure **104L** may comprise silicon dioxide, carbon doped silicon dioxide, silicon oxynitride, BSG, PSG, BPSG, FSG, a porous dielectric material, or the like. In some embodiments, the lower dielectric structure **104L** may be formed by one or more deposition processes (e.g., a physical vapor deposition (PVD) process, a chemical vapor deposition (CVD) process, a plasma enhanced chemical vapor deposition (PE-CVD) process, an atomic layer deposition (ALD) process, etc.) and the conductive material (e.g., tungsten, copper, aluminum, or the like) may be formed using a deposition process and/or a plating process (e.g., electroplating, electro-less plating, etc.).

[0089] As shown in cross-sectional view **1200** of FIG. **12**, a first upper dielectric structure **1201** is formed over the lower dielectric structure **104L**. In some embodiments, the first upper dielectric structure **1201** comprises a first bond pad etch stop layer **105b** formed over the lower dielectric structure **104L** and a first bond pad ILD layer **104c** formed on the first bond pad etch stop layer **105b**. In some embodiments, the first bond pad etch stop layer **105b** may comprise a nitride (e.g., silicon nitride, silicon oxynitride, etc.), a carbide (e.g., silicon carbide, silicon oxycarbide, etc.), or the like. In some embodiments, the first bond pad ILD layer **104c** may comprise silicon dioxide, carbon doped silicon dioxide, silicon oxynitride, BSG, PSG, BPSG, FSG, a porous dielectric material, or the like. In some embodiments, the first bond pad etch stop layer **105b** and the first bond pad ILD layer **104c** may be formed by way of deposition processes (e.g., a PVD process, a CVD process, a PE-CVD process, an ALD process, etc.).

[0090] A first bond pad opening **1202** is formed within the first upper dielectric structure **1201**. In some embodiments, the first bond pad opening **1202** may be formed according to a first patterning process. In some embodiments, the first patterning process may be performed by selectively exposing the first upper dielectric structure **1201** to a first etchant **1204** according to a first mask **1206**. The first patterning process forms sidewalls of first upper dielectric structure **1201**, which define the first bond pad opening **1202**. In some embodiments, the first etchant **1204** may comprise a plasma etchant having a fluorine based etching chemistry (e.g., a SF₆ plasma, or the like). In some embodiments, the first mask **1206** may comprise a photosensitive material (e.g., a photoresist), a hard mask, or the like.

[0091] As shown in cross-sectional view **1300** of FIG. **13**, a first barrier layer **114b** and a first conductive core **114c** are formed within the first bond pad opening **1202**. In such embodiments, the first barrier layer **114b** may be formed along interior surfaces of the first upper dielectric structure **1201** defining the first bond pad opening **1202**. The first conductive core **114c** may be subsequently formed over the first barrier layer **114b** and within the first bond pad opening **1202**. In some embodiments, the first barrier layer **114b** may be formed by way of a deposition process (e.g., a PVD process, a CVD process, a PE-CVD process, an ALD process, etc.). In some embodiments, the first conductive core **114c** may be formed by depositing a first conductive material using a deposition process and/or a plating process (e.g., electroplating, electro-less plating, etc.). In various embodiments, the first barrier layer **114b** may comprise titanium, tantalum, titanium nitride, tantalum nitride, or the like. In various embodiments, the first conductive material may

comprise copper, aluminum, tungsten, or the like. After depositing the first conductive material within the first bond pad opening **1202**, a planarization process may be performed to remove excess of the first conductive material from over the first upper dielectric structure **1201** and to define a lower segment **114** of a bond pad. In some embodiments, the planarization process may comprise a chemical mechanical polishing (CMP) process. In other embodiments, the planarization process may comprise an etching process and/or a grinding process, for example.

[0092] As shown in cross-sectional view **1400** of FIG. **14**, a second upper dielectric structure **1401** is formed over the first upper dielectric structure **1201**. In some embodiments, the second upper dielectric structure **1401** comprises a second bond pad etch stop layer **105c** formed over the first bond pad ILD layer **104c**, a second bond pad ILD layer **104d** formed on the second bond pad etch stop layer **105c**, and a top dielectric layer **105t** formed on the second bond pad ILD layer **104d**. In some embodiments, the second bond pad etch stop layer **105c** and/or the top dielectric layer **105t** may comprise a nitride (e.g., silicon nitride, silicon oxynitride, etc.), a carbide (e.g., silicon carbide, silicon oxycarbide, etc.), or the like. In some embodiments, the second bond pad ILD layer **104d** may comprise silicon dioxide, carbon doped silicon dioxide, silicon oxynitride, BSG, PSG, BPSG, FSG, a porous dielectric material, or the like. In some embodiments, the second bond pad etch stop layer **105c**, the second bond pad ILD layer **104d**, and the top dielectric layer **105t** may be formed by way of deposition processes (e.g., a PVD process, a CVD process, a PE-CVD process, an ALD process, etc.).

[0093] As shown in cross-sectional view **1500** of FIG. **15**, a second bond pad opening **1502** is formed within the second upper dielectric structure **1401**. In some embodiments, the second bond pad opening **1502** may be formed according to a second patterning process. In some embodiments, the second patterning process may be performed by selectively exposing the second upper dielectric structure **1401** to a second etchant **1504** according to a second mask **1506**. The second patterning process forms sidewalls of the second upper dielectric structure **1401** that define the second bond pad opening **1502**. In some embodiments, the second etchant **1504** may comprise a plasma etchant having a fluorine based etching chemistry (e.g., a SF₆ plasma, or the like). In some embodiments, the second mask **1506** may comprise a photosensitive material (e.g., a photoresist), a hard mask, or the like.

[0094] As shown in cross-sectional view **1600** of FIG. **16**, a barrier material **1602** and a second conductive material **1604** are formed within the second bond pad opening **1502** and over the top dielectric layer **105t**. The barrier material **1602** may be formed along interior surfaces defining the second bond pad opening **1502**. The second conductive material **1604** may be subsequently formed over the barrier material **1602** and within the second bond pad opening **1502**. In some embodiments, the barrier material **1602** may be formed by way of a deposition process (e.g., a PVD process, a CVD process, a PE-CVD process, an ALD process, etc.). In some embodiments, the second conductive material **1604** may be formed by way of a deposition process and/or a plating process (e.g., electroplating, electro-less plating, etc.). In various embodiments, the barrier material **1602** may comprise titanium, tantalum, titanium nitride, tantalum nitride, or the like. In various embodiments, the second conductive material may comprise copper, aluminum, tungsten, or the like.

[0095] As shown in cross-sectional view **1700** of FIG. **17A** and top-view **1706** of FIG. **17B**, after forming the second conductive material (e.g., **1604** of FIG. **16**) within the second bond pad opening (e.g., **1502** of FIG. **16**), a planarization process may be performed (along line **1702**). The planarization process removes excess of the second conductive material from over the top dielectric layer **105t** to define an upper segment **116** of a bond pad **112** on a first IC die **202**. The upper segment **116** of the bond pad **112** comprises a second barrier layer **116b** and a second conductive core **116c** over the second barrier layer **116b**. The upper segment **116** of the bond pad **112** comprises a top surface having a plurality of discrete top surface segments **112u** that are laterally separated from one another by one or more cavities **113** defined by interior sidewalls of the bond

pad **112**, as viewed in the cross-sectional view **1700**. The one or more cavities **113** are filled with the second upper dielectric structure (e.g., the top dielectric layer **105t**, the second bond pad ILD layer **104d**, and the second bond pad etch stop layer **105c**).

[0096] In some embodiments, the planarization process may comprise a chemical mechanical polishing (CMP) process. During the CMP process an upper surface of the first IC die **202** is brought into contact with a polishing pad **1704**, so that the top dielectric layer **105t** and the upper segment **116** of the bond pad **112** are brought into contact with the polishing pad **1704**. Because the top dielectric layer **105t** is disposed directly between interior sidewalls of the upper segment **116** of the bond pad **112**, an overlap between the polishing pad **1704** and individual ones of the plurality of discrete top surface segments **112u** is reduced. Reducing the overlap between the polishing pad **1704** and individual ones of the plurality of discrete top surface segments **112u** reduces a dishing of individual ones of the plurality of discrete top surface segments **112u**.

[0097] As shown in cross-sectional view **1800** of FIG. **18**, the bond pad **112** of first IC die **202** is bonded to the additional bond pad **218** of a second IC die **208** to form a multi-dimensional integrated chip structure. During bonding, the plurality of discrete top surface segments of the bond pad **112** are brought into contact with a plurality of discrete segments of the additional bond pad **218**. Furthermore, top surfaces of the dielectric structure **104** are brought into contact with surfaces of an additional dielectric structure **210** of the second IC die **208**, so as to form a hybrid bonding interface between the first IC die **202** and the second IC die **208**. The reduced dishing of the plurality of discrete top surface segments of the bond pad **112** decreases formation of voids between the bond pad **112** and the additional bond pad **218**, thereby improving an electrical performance and/or a reliability of the multi-dimensional integrated chip structure.

[0098] FIGS. **19-28** illustrate some additional embodiments of a method of forming an integrated chip structure comprising a disclosed bond pad having one or more cavities configured to reduce dishing of the bond pad. Although FIGS. **19-28** are described in relation to a method, it will be appreciated that the structures disclosed in FIGS. **19-28** are not limited to such a method, but instead may stand alone as structures independent of the method.

[0099] As shown in cross-sectional view **1900** of FIG. **19**, a substrate **102** is provided. One or more interconnects **106** are formed within a lower dielectric structure **104L** formed over a substrate **102**. In some embodiments, the one or more interconnects **106** may comprise a topmost interconnect **108** comprising a barrier layer **108b** and a conductive core **108c**.

[0100] As shown in cross-sectional view **2000** of FIG. **20**, a first upper dielectric structure **2001** is formed over the lower dielectric structure **104L**. In some embodiments, the first upper dielectric structure **2001** comprises a first bond pad etch stop layer **105b** formed over the lower dielectric structure **104L**, a first bond pad ILD layer **104c** formed on the first bond pad etch stop layer **105b**, a second bond pad etch stop layer **105c** formed on the first bond pad ILD layer **104c**, and a second bond pad ILD layer **104d** formed on the second bond pad etch stop layer **105c**.

[0101] An intermediate first bond pad opening **2002** is formed within the first upper dielectric structure **2001**. In some embodiments, the intermediate first bond pad opening **2002** may be formed according to a first patterning process. In some embodiments, the first patterning process may be performed by selectively exposing the first upper dielectric structure **2001** to a first etchant **2004** according to a first mask **2006**.

[0102] As shown in cross-sectional view **2100** of FIG. **21**, a sacrificial mask **2102** is formed within the intermediate first bond pad opening **2002**. The sacrificial mask **2102** may comprise a dielectric material, a photoresist material, or the like.

[0103] As shown in cross-sectional view **2200** of FIG. **22**, a first bond pad opening **2202** is formed within the first upper dielectric structure **2001**. In some embodiments, the first bond pad opening **2202** may be formed according to a second patterning process. In some embodiments, the second patterning process may be performed by selectively exposing the first upper dielectric structure **2001** to a second etchant **2204** according to a second mask **2206**.

[0104] As shown in cross-sectional view **2300** of FIG. **23**, the sacrificial mask (e.g., **2102** of FIG. **22**) is removed from within the first bond pad opening **2202**. In various embodiments, the sacrificial mask **2102** may be removed by way of a chemical developer, an etching process, or the like.

[0105] As shown in cross-sectional view **2400** of FIG. **24**, a first barrier layer **114b** is formed within the first bond pad opening **2202** and a first conductive core **114c** is formed on the first barrier layer **114b** and within the first bond pad opening **2202**. In such embodiments, the first barrier layer **114b** may be formed along interior surfaces defining the first bond pad opening **2202**. The first conductive core **114c** may be subsequently formed over the barrier layer **114b** and within the first bond pad opening **2202**.

[0106] As shown in cross-sectional view **2500** of FIG. **25**, a second upper dielectric structure **2501** is formed over the first upper dielectric structure **2001**. In some embodiments, the second upper dielectric structure **2501** comprises a third bond pad etch stop layer **105d** formed over the second bond pad ILD layer **104d**, a third bond pad ILD layer **104e** formed on the third bond pad etch stop layer **105d**, and a top dielectric layer **105t** formed over the third bond pad ILD layer **104e**.

[0107] A second bond pad opening **2502** is formed within the second upper dielectric structure **2501**. In some embodiments, the second bond pad opening **2502** may be formed according to a third patterning process. In some embodiments, the third patterning process may be performed by selectively exposing the second upper dielectric structure **2501** to a third etchant **2504** according to a third mask **2506**. The third patterning process forms sidewalls of the second upper dielectric structure **2501** that define the second bond pad opening **2502**.

[0108] As shown in cross-sectional view **2600** of FIG. **26**, a barrier material **2602** and a conductive material **2604** are formed within the second bond pad opening **2502** and over the top dielectric layer **105t**. In such embodiments, the barrier material **2602** may be formed along interior surfaces defining the second bond pad opening **2502**. The conductive material **2604** may be subsequently formed over the barrier material **2602** and within the second bond pad opening **2502**.

[0109] As shown in cross-sectional view **2700** of FIG. **27A** and top-view **2706** of FIG. **27B**, after forming the conductive material (e.g., **2604** of FIG. **26**) within the second bond pad opening **2502**, a planarization process may be performed (along line **2702**). The planarization process removes excess of the conductive material from over the second upper dielectric structure to define an upper segment **116** of a bond pad **112** on a first IC die **202**. The upper segment **116** of the bond pad **112** comprises a part of the first barrier layer **114b**, a part of the first conductive core **114c**, a second barrier layer **116b**, and a second conductive core **116c** over the second barrier layer **116b**. The upper segment **116** of the bond pad **112** comprises a top surface comprises a plurality of discrete top surface segments **112u** that are laterally separated from one another by one or more cavities **113** that are defined by interior sidewalls of the bond pad **112**. The one or more cavities **113** are filled with the second upper dielectric structure.

[0110] In some embodiments, the planarization process may comprise a chemical mechanical polishing (CMP) process. During the CMP process an upper surface of the first IC die **202** is brought into contact with a polishing pad **2704**, so that the top dielectric layer **105t** and the upper segment **116** of the bond pad **112** are brought into contact with the polishing pad **2704**. Because the top dielectric layer **105t** is disposed directly between interior sidewalls of the upper segment **116** of the bond pad **112**, an overlap between the polishing pad **2704** and individual ones of the plurality of discrete top surface segments **112u** is reduced. Reducing the overlap between the polishing pad **1704** and individual ones of the plurality of discrete top surface segments **112u** reduces a dishing of individual ones of the plurality of discrete top surface segments **112u**.

[0111] As shown in cross-sectional view **2800** of FIG. **28**, the bond pad **112** of first IC die **202** is bonded to the additional bond pad **218** of a second IC die **208**. During bonding, the plurality of discrete top surface segments of the bond pad **112** are brought into contact with a plurality of additional discrete segments of the additional bond pad **218**. Furthermore, upper surfaces of the

dielectric structure **104** are brought into contact with surfaces of an additional dielectric structure **210** of the second IC die **208**, so as to form a hybrid bonding interface between the first IC die **202** and the second IC die **208**.

[0112] In some alternative embodiments, the acts of FIGS. **25-27B** may be omitted and a first die having a bond pad with the structure of FIG. **24** may be bonded to an additional die having a bond pad with the structure of FIG. **24** along a hybrid bonding interface (e.g., extending along tops of the first barrier layer **114b** and the first conductive core **114c**).

[0113] FIGS. **29-35** illustrate some additional embodiments of a method of forming an integrated chip structure comprising a disclosed bond pad having one or more cavities configured to reduce dishing of the bond pad. Although FIGS. **29-35** are described in relation to a method, it will be appreciated that the structures disclosed in FIGS. **29-35** are not limited to such a method, but instead may stand alone as structures independent of the method.

[0114] As shown in cross-sectional view **2900** of FIG. **29**, a substrate **102** is provided. One or more interconnects **106** are formed within a lower dielectric structure **104L** formed over a substrate **102**. In some embodiments, the one or more interconnects **106** may comprise a topmost interconnect **108** comprising a barrier layer **108b** and a conductive core **108c**.

[0115] As shown in cross-sectional view **3000** of FIG. **30**, a first upper dielectric structure **3001** is formed over the lower dielectric structure **104L**. In some embodiments, the first upper dielectric structure **3001** comprises a first bond pad etch stop layer **105b** formed over the lower dielectric structure **104L** and a first bond pad ILD layer **104c** formed on the first bond pad etch stop layer **105b**. One or more first bond pad openings **3002** are formed within the first upper dielectric structure **3001**. In some embodiments, the one or more first bond pad openings **3002** may be formed according to a first patterning process. In some embodiments, the first patterning process may be performed by selectively exposing the first upper dielectric structure **3001** to a first etchant **3004** according to a first mask **3006**.

[0116] As shown in cross-sectional view **3100** of FIG. **31A**, a first barrier layer **114b** and a first conductive core **114c** are formed within the one or more first bond pad openings **3002**. In some embodiments, the first barrier layer **114b** may be formed along interior surfaces of the first upper dielectric structure **3001** defining the one or more first bond pad openings **3002**. The first conductive core **114c** may be subsequently formed over the first barrier layer **114b** and within the one or more first bond pad openings **3002**. After depositing the first conductive material within the one or more first bond pad openings **3002**, a planarization process may be performed to remove excess of the first conductive material from over the first upper dielectric structure **3001** and to define a lower segment **114** of a bond pad.

[0117] In some embodiments, shown in top-view **3102** of FIG. **31B**, the lower segment **114** of the bond pad may comprise a plurality of discrete lower segments **114d**. The plurality of discrete lower segments **114d** may be formed in an array. The plurality of discrete lower segments **114d** may be separated along a first direction **120** and along a second direction **122** that is perpendicular to the first direction **120**. In some embodiments, cross-sectional view **3100** of FIG. **31A** is taken along cross-sectional line A-A' of FIG. **31B**.

[0118] In some alternative embodiments, shown in top-view **3104** of FIG. **31C**, the lower segment **114** of the bond pad may comprise a single continuous segment that continuously extends in a closed loop around one or more cavities **113**. In some embodiments, the one or more cavities **113** respectively have a rectangular shape. In some embodiments, cross-sectional view **3100** of FIG. **31A** is taken along cross-sectional line A-A' of FIG. **31C**.

[0119] As shown in cross-sectional view **3200** of FIG. **32**, a second upper dielectric structure **3201** is formed over the first upper dielectric structure **3001**. In some embodiments, the second upper dielectric structure **3201** comprises a second bond pad etch stop layer **105c** formed over the first bond pad ILD layer **104c**, a second bond pad ILD layer **104d** formed on the second bond pad etch stop layer **105c**, and a top dielectric layer **105t** formed over the second bond pad ILD layer **104d**.

[0120] As shown in cross-sectional view **3300** of FIG. **33**, one or more second bond pad openings **3302** are formed within the second upper dielectric structure **3201**. In some embodiments, the one or more second bond pad openings **3302** may be formed according to a third patterning process. In some embodiments, the third patterning process may be performed by selectively exposing the second upper dielectric structure **3201** to a third etchant **3304** according to a third mask **3306**. The third patterning process forms sidewalls of the second upper dielectric structure **3201** that define the one or more second bond pad openings **3302**.

[0121] As shown in cross-sectional view **3400** of FIG. **34A**, a second barrier layer **116b** and a second conductive core **116c** are formed within the one or more second bond pad openings **3302**. In some embodiments, the second barrier layer **116b** may be formed along interior surfaces of the second upper dielectric structure **3201** defining the one or more second bond pad openings **3302**. The second conductive core **116c** may be subsequently formed over the second barrier layer **116b** and within the one or more second bond pad openings **3302**. A planarization process may be performed to remove parts of the second barrier layer **116b** and the second conductive core **116c** to form an upper segment **116** of a bond pad.

[0122] In some embodiments, shown in top-view **3402** of FIG. **34B**, the upper segment **116** of the bond pad may comprise a plurality of discrete upper segments **116d**. The plurality of discrete upper segments **116d** may be formed in an array. The plurality of discrete upper segments **116d** may be separated along the first direction **120** and along the second direction **122**. In some embodiments, cross-sectional view **3400** of FIG. **34A** is taken along cross-sectional line A-A' of FIG. **34B**.

[0123] In some alternative embodiments, shown in top-view **3404** of FIG. **34C** and top-view **3406** of FIG. **34D**, the upper segment **116** of the bond pad may comprise a single continuous segment that continuously extends in a closed loop around one or more cavities **113**. In some embodiments, the single continuous segment may directly overlie a plurality of discrete lower segments **114d** (e.g., as shown in FIG. **31B**), while in other embodiments the single continuous segment may directly overlie a single continuous lower segment (e.g., as shown in FIG. **31C**). In some embodiments, cross-sectional view **3400** of FIG. **34A** is taken along cross-sectional line A-A' of FIG. **34C** or along cross-sectional line A-A' of FIG. **34D**.

[0124] As shown in cross-sectional view **3500** of FIG. **35**, the bond pad **112** of first IC die **202** is bonded to the additional bond pad **218** of a second IC die **208**. During bonding, the plurality of discrete top surface segments of the bond pad **112** are brought into contact with a plurality of additional discrete segments of the additional bond pad **218**. Furthermore, upper surfaces of the dielectric structure **104** are brought into contact with surfaces of an additional dielectric structure **210** of the second IC die **208**, so as to form a hybrid bonding interface between the first IC die **202** and the second IC die **208**.

[0125] FIG. **36** illustrates a flow diagram of some embodiments of a method **3600** of forming an integrated chip structure comprising a disclosed bond pad having one or more cavities configured to reduce dishing of the bond pad.

[0126] While method **3600** is illustrated and described herein as a series of acts or events, it will be appreciated that the illustrated ordering of such acts or events are not to be interpreted in a limiting sense. For example, some acts may occur in different orders and/or concurrently with other acts or events apart from those illustrated and/or described herein. In addition, not all illustrated acts may be required to implement one or more aspects or embodiments of the description herein. Further, one or more of the acts depicted herein may be carried out in one or more separate acts and/or phases.

[0127] At act **3602**, one or more interconnects are formed within a lower dielectric structure over a substrate. FIG. **11** illustrates a cross-sectional view **1100** of some embodiments corresponding to act **3602**. FIG. **19** illustrates a cross-sectional view **1900** of some additional embodiments corresponding to act **3602**. FIG. **29** illustrates a cross-sectional view **2900** of some additional embodiments corresponding to act **3602**.

[0128] At act **3604**, a first upper dielectric structure is formed over the lower dielectric structure. FIG. **12** illustrates a cross-sectional view **1200** of some embodiments corresponding to act **3604**. FIG. **20** illustrates a cross-sectional view **2000** of some additional embodiments corresponding to act **3604**. FIG. **30** illustrates a cross-sectional view **3000** of some additional embodiments corresponding to act **3604**.

[0129] At act **3606**, a first bond pad opening is formed within the first upper dielectric structure. FIG. **12** illustrates a cross-sectional view **1200** of some embodiments corresponding to act **3606**. FIGS. **20-23** illustrate cross-sectional views **2000-2300** of some additional embodiments corresponding to act **3606**. FIG. **30** illustrates a cross-sectional view **3000** of some additional embodiments corresponding to act **3606**.

[0130] At act **3608**, a first barrier layer and a first conductive core are formed within the first bond pad opening. FIG. **13** illustrates a cross-sectional view **1300** of some embodiments corresponding to act **3608**. FIG. **24** illustrates a cross-sectional view **2400** of some additional embodiments corresponding to act **3608**. FIG. **31A** illustrates a cross-sectional view **3100** of some additional embodiments corresponding to act **3608**.

[0131] At act **3610**, a second upper dielectric structure is formed over the first upper dielectric structure. FIG. **14** illustrates a cross-sectional view **1400** of some embodiments corresponding to act **3610**. FIG. **25** illustrates a cross-sectional view **2500** of some additional embodiments corresponding to act **3610**. FIG. **32** illustrates a cross-sectional view **3200** of some additional embodiments corresponding to act **3610**.

[0132] At act **3612**, a second bond pad opening is formed within the second upper dielectric structure to expose the first conductive core and to surround one or more interior sidewalls of the second upper dielectric structure. FIG. **15** illustrates a cross-sectional view **1500** of some embodiments corresponding to act **3612**. FIG. **25** illustrates a cross-sectional view **2500** of some additional embodiments corresponding to act **3612**. FIG. **33** illustrates a cross-sectional view **3300** of some additional embodiments corresponding to act **3612**.

[0133] At act **3614**, a barrier material and a conductive material are formed within the second bond pad opening. FIG. **16** illustrates a cross-sectional view **1600** of some embodiments corresponding to act **3614**. FIG. **26** illustrates a cross-sectional view **2600** of some additional embodiments corresponding to act **3614**. FIG. **34A** illustrates a cross-sectional view **3400** of some additional embodiments corresponding to act **3614**.

[0134] At act **3616**, a chemical mechanical planarization (CMP) process is performed to remove parts of the barrier material and the conductive material so as to define a bond pad having interior sidewalls that form one or more cavities extending into the bond pad. The interior sidewalls are coupled to a top of the bond pad. FIGS. **17A-17B** illustrate some embodiments corresponding to act **3616**. FIGS. **27A-27B** illustrate some additional embodiments corresponding to act **3616**. FIG. **34A** illustrates a cross-sectional view **3400** of some additional embodiments corresponding to act **3616**.

[0135] At act **3618**, an integrated chip die comprising the bond pad is brought into contact with an additional integrated chip die comprising an additional bond pad along a hybrid bonding interface. FIG. **18** illustrates a cross-sectional view **1800** of some embodiments corresponding to act **3618**. FIG. **28** illustrates a cross-sectional view **2800** of some additional embodiments corresponding to act **3618**. FIG. **35** illustrates a cross-sectional view **3500** of some additional embodiments corresponding to act **3618**.

[0136] Accordingly, the present disclosure relates to an integrated chip structure having a bond pad with one or more cavities that are surrounded by the bond pad and that are filled with a dielectric material that is configured to mitigate dishing along an upper surface of the bond pad

[0137] In some embodiments, the present disclosure relates to an integrated chip structure. The integrated chip structure includes one or more interconnects disposed within a dielectric structure over a substrate; a bond pad having a top surface arranged along a top surface of the dielectric

structure, the top surface of the bond pad including a plurality of discrete top surface segments that are laterally separated from one another by one or more non-zero distances that extend between interior sidewalls of the bond pad, as viewed in a cross-sectional view; and the dielectric structure being disposed directly between the interior side walls of the bond pad. In some embodiments, a bottom surface of the bond pad laterally and continuously extends past one or more of the interior sidewalls of the bond pad. In some embodiments, the top surface of the bond pad is substantially co-planar with the top surface of the dielectric structure. In some embodiments, the one or more interconnects include a topmost interconnect disposed within the dielectric structure, the topmost interconnect having an upper surface that directly contacts a bottom surface of the bond pad and that continuously extends past outermost sidewalls of the bottom surface of the bond pad. In some embodiments, the one or more interconnects include a topmost interconnect disposed within the dielectric structure, the dielectric structure between the interior sidewalls of the bond pad continuously extending from the top surface of the dielectric structure to the topmost interconnect. In some embodiments, the bond pad includes a lower segment laterally extending between opposing sidewalls coupled to a bottom of the bond pad; and an upper segment having a lower surface disposed onto an upper surface of the lower segment, the upper segment laterally extending between opposing outermost sidewalls of the bond pad. In some embodiments, the lower surface of the upper segment physically contacts the upper surface of the lower segment. In some embodiments, the interior sidewalls of the bond pad are arranged within the upper segment and are coupled to horizontally extending surfaces that are directly above the lower surface of the upper segment. In some embodiments, the bond pad continuously wraps extends in an unbroken loop, as viewed in a top-view of the bond pad.

[0138] In other embodiments, the present disclosure relates to an integrated chip structure. The integrated chip structure includes one or more interconnects surrounded by a dielectric structure disposed on a substrate; a bond pad surrounded by the dielectric structure and having a lower segment extending between outer edges of lower sidewalls arranged along a bottom of the bond pad, and an upper segment extending between outer edges of upper sidewalls arranged along a top of the bond pad; and the upper segment of the bond pad including one or more interior sidewalls separated by non-zero distances between edges of a top surface of the bond pad, the dielectric structure being between the edges of the top surface of the bond pad. In some embodiments, the upper segment has a lower surface that continuously extends past opposing outer edges of the lower segment. In some embodiments, the further integrated chip structure includes one or more additional interconnects surrounded by an additional dielectric structure disposed on a second substrate; an additional bond pad surrounded by the additional dielectric structure and having one or more additional interior sidewalls separated by the additional dielectric structure; and the bond pad contacting the additional bond pad along a conductive interface and the dielectric structure between edges of the top surface of the bond pad contacting the additional dielectric structure separating the one or more additional sidewalls along a dielectric interface. In some embodiments, the upper sidewalls vertically extend below a top of the lower sidewalls. In some embodiments, the upper segment includes a barrier layer and a conductive core, the dielectric structure contacting sidewalls of the barrier layer. In some embodiments, the top surface of the bond pad includes a plurality of discrete top surface segments as viewed in a cross-sectional view of the bond pad, the plurality of discrete top surface segments being separated from one another by the non-zero distances. In some embodiments, the interior sidewalls of the bond pad are further coupled to a horizontally extending surface of the bond pad that faces away from the substrate. In some embodiments, the bond pad includes an outer ring segment that continuously extends in an unbroken loop.

[0139] In yet other embodiments, the present disclosure relates to a method of forming an integrated chip structure. The method includes forming a first bond pad opening within a first upper dielectric structure formed over a lower dielectric structure surrounding one or more interconnects

over a substrate; forming a first barrier layer and a first conductive core within the first bond pad opening; forming a second upper dielectric structure over the first upper dielectric structure; forming a second bond pad opening within the second upper dielectric structure to expose the first conductive core and to surround one or more interior sidewalls of the second upper dielectric structure; forming a barrier material and a conductive material within the second bond pad opening; and removing parts of the barrier material and the conductive material, removing the parts of the barrier material and the conductive material forming a bond pad having interior sidewalls that form one or more cavities extending into the bond pad. In some embodiments, the one or more cavities are filled with the second upper dielectric structure. In some embodiments, the bond pad has a plurality of discrete upper surfaces that are separated from one another by the second upper dielectric structure, as viewed along a cross-sectional view.

[0140] The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. An integrated chip structure, comprising: one or more interconnects disposed within a dielectric structure over a substrate; a bond pad having a top surface arranged along a top surface of the dielectric structure, wherein the top surface of the bond pad comprises a plurality of discrete top surface segments that are laterally separated from one another by one or more non zero distances that extend between interior sidewalls of the bond pad, as viewed in a cross-sectional view; and wherein the dielectric structure is disposed directly between the interior sidewalls of the bond pad.
2. The integrated chip structure of claim 1, wherein a bottom surface of the bond pad laterally and continuously extends past one or more of the interior sidewalls of the bond pad.
3. The integrated chip structure of claim 1, wherein the top surface of the bond pad is substantially co-planar with the top surface of the dielectric structure.
4. The integrated chip structure of claim 1, wherein the one or more interconnects comprise a topmost interconnect disposed within the dielectric structure, the topmost interconnect having an upper surface that directly contacts a bottom surface of the bond pad and that continuously extends past outermost sidewalls of the bottom surface of the bond pad.
5. The integrated chip structure of claim 1, wherein the one or more interconnects comprise a topmost interconnect disposed within the dielectric structure, the dielectric structure between the interior sidewalls of the bond pad continuously extending from the top surface of the dielectric structure to the topmost interconnect.
6. The integrated chip structure of claim 1, wherein the bond pad comprises: a lower segment laterally extending between opposing sidewalls coupled to a bottom of the bond pad; and an upper segment having a lower surface disposed onto an upper surface of the lower segment, the upper segment laterally extending between opposing outermost sidewalls of the bond pad.
7. The integrated chip structure of claim 6, wherein the lower surface of the upper segment physically contacts the upper surface of the lower segment.
8. The integrated chip structure of claim 6, wherein the interior sidewalls of the bond pad are arranged within the upper segment and are coupled to horizontally extending surfaces that are directly above the lower surface of the upper segment.
9. The integrated chip structure of claim 1, wherein the bond pad continuously extends in an

unbroken loop, as viewed in a top-view of the bond pad.

10. An integrated chip structure, comprising: one or more interconnects surrounded by a dielectric structure disposed on a substrate; a bond pad surrounded by the dielectric structure and comprising a lower segment extending between outer edges of lower sidewalls arranged along a bottom of the bond pad, and an upper segment extending between outer edges of upper sidewalls arranged along a top surface of the bond pad; and wherein the upper segment of the bond pad comprises one or more interior sidewalls separated by non-zero distances between edges of the top surface of the bond pad, the dielectric structure being between the edges of the top surface of the bond pad.

11. The integrated chip structure of claim 10, wherein the upper segment has a lower surface that continuously extends past opposing outer edges of the lower segment.

12. The integrated chip structure of claim 10, further comprising: one or more additional interconnects surrounded by an additional dielectric structure disposed on a second substrate; an additional bond pad surrounded by the additional dielectric structure and comprising one or more additional interior sidewalls separated by the additional dielectric structure; and wherein the bond pad contacts the additional bond pad along a conductive interface and the dielectric structure between edges of the top surface of the bond pad contacts the additional dielectric structure separating the one or more additional interior sidewalls along a dielectric interface.

13. The integrated chip structure of claim 10, wherein the upper sidewalls vertically extend below a top of the lower sidewalls.

14. The integrated chip structure of claim 10, wherein the upper segment comprises a barrier layer and a conductive core, the dielectric structure contacting sidewalls of the barrier layer.

15. The integrated chip structure of claim 10, wherein the top surface of the bond pad comprises a plurality of discrete top surface segments as viewed in a cross-sectional view of the bond pad, the plurality of discrete top surface segments being separated from one another by the non-zero distances.

16. The integrated chip structure of claim 10, wherein the interior sidewalls of the bond pad are further coupled to a horizontally extending surface of the bond pad that faces away from the substrate.

17. The integrated chip structure of claim 10, wherein the bond pad comprises an outer ring segment that continuously extends in an unbroken loop.

18. An integrated chip structure, comprising: one or more interconnects surrounded by a dielectric structure on a substrate; a bond pad arranged over the one or more interconnects and laterally surrounded by the dielectric structure, the bond pad comprising a lower segment and an upper segment over the lower segment; and wherein the upper segment of the bond pad laterally extends past a sidewall of the lower segment and comprises one or more interior sidewalls coupled to one or more top surfaces of the bond pad and surrounding a part of the dielectric structure.

19. The integrated chip structure of claim 18, further comprising: an additional bond pad disposed on a second substrate and surrounded by an additional dielectric structure, the additional bond pad comprising one or more additional interior sidewalls separated by the additional dielectric structure; and wherein the bond pad contacts the additional bond pad in a cross-sectional view.

20. The integrated chip structure of claim 19, wherein the part of the dielectric structure contacts a part of the additional dielectric structure that is between the one or more additional interior sidewalls in the cross-sectional view.
