

# US Patent & Trademark Office

## Patent Public Search | Text View

---

United States Patent Application Publication

20250266406

Kind Code

A1

Publication Date

August 21, 2025

Inventor(s)

LI; Qiming et al.

---

## SYSTEM AND METHODS FOR MULTI-COLOR LED PIXEL UNIT

---

### Abstract

A micro multi-color LED device includes two or more LED structures for emitting a range of colors. The two or more LED structures are vertically stacked to combine light from the two more LED structures. Light from the micro multi-color LED device is emitted horizontally from each of the LED structures and reflected upward via some reflective structures. In some embodiments, each LED structure is connected to a pixel driver and/or a common electrode. The LED structures are bonded together through bonding layers. In some embodiments, planarization layers enclose each of the LED structures or the micro multi-color LED device. In some embodiments, one or more of reflective layers, refractive layers, micro-lenses, spacers, and reflective cup structures are implemented in the device to improve the LED emission efficiency. A display panel comprising an array of the micro tri-color LED devices has a high resolution and a high illumination brightness.

---

**Inventors:** LI; Qiming (Albuquerque, NM), Xu; Qunchao (Shanghai, CN), Xu; Huiwen (Shanghai, CN)

**Applicant:** Jade Bird Display (Shanghai) Limited (Shanghai, CN)

**Family ID:** 1000008574755

**Assignee:** Jade Bird Display (Shanghai) Limited (Shanghai, CN)

**Appl. No.:** 19/063124

**Filed:** February 25, 2025

### Related U.S. Application Data

parent US continuation 17620661 20211217 parent-grant-document US 12272682 US continuation PCT/US2020/038785 20200619 child US 19063124

us-provisional-application US 63034394 20200603

us-provisional-application US 63034391 20200603

us-provisional-application US 63013370 20200421

## Publication Classification

**Int. Cl.:** **H01L25/075** (20060101); **H01L25/16** (20230101); **H10H20/831** (20250101);  
**H10H20/856** (20250101)

**U.S. Cl.:**

**CPC** **H01L25/0756** (20130101); **H01L25/167** (20130101); **H10H20/8312** (20250101);  
**H10H20/856** (20250101);

---

## Background/Summary

RELATED APPLICATION [0001] This application is a continuation application of U.S. patent application Ser. No. 17/620,661, filed on Dec. 17, 2021, entitled “Systems and Methods for Multi-Color LED Pixel Unit,” which is a national phase entry under 35 U.S.C. § 371 from PCT International Application No. PCT/US2020/038785, filed Jun. 19, 2020. PCT International Application No. PCT/US2020/038785 claims priority to U.S. Provisional Patent Application No. 62/863,559, filed Jun. 19, 2019, entitled “Systems and Methods for Coaxial Multi-Color LED;” U.S. Provisional Patent Application No. 63/013,358, filed Apr. 21, 2020, entitled “Light-Emitting Diode Chip Structures with Reflective Elements;” U.S. Provisional Patent Application No. 63/013,370, filed Apr. 21, 2020, entitled “Light-Emitting Diode Chip Structures with Reflective Elements;” U.S. Provisional Patent Application No. 63/034,391, filed Jun. 3, 2020, entitled “Systems and Methods for Multi-Color LED Pixel Unit with Vertical Light Emission;” and U.S. Provisional Patent Application No. 63/034,394, filed Jun. 3, 2020, entitled “Systems and Methods for Multi-Color LED Pixel Unit with Horizontal Light Emission.” The contents of the above patent applications are incorporated herein in their entirety by reference.

## TECHNICAL FIELD

[0002] The present disclosure relates generally to light-emitting diode (LED) display devices, and more particularly, to systems and fabricating methods for LED semiconductor devices that emit different colors with high brightness and micro-meter scale pixel size.

## BACKGROUND

[0003] With the development of Mini LED and Micro LED technology in recent years, consumer devices and applications such as augmented reality (AR), Virtual Reality (VR), projection, heads-up display (HUD), mobile device displays, wearable device displays, and automotive displays, require LED panels with improved resolution and brightness. For example, an AR display integrated within a goggle and positioned close to a wearer's eyes can have a dimension of a fingernail while still demanding an HD definition (1280×720 pixels) or higher. Many electronic devices require certain pixel size, distance between adjacent pixels, brightness, and viewing angle for the LED panels. Often, when trying to achieve the maximum resolution and brightness on a small display, it is challenging to maintain both the resolution and brightness requirements. In contrast, in some cases, pixel size and brightness are difficult to balance at the same time as they can have an approximately opposite relationship. For example, getting a high brightness for each pixel could result in a low resolution. Alternatively, obtaining a high resolution could bring the brightness down.

[0004] Generally, at least red, green and blue colors are superimposed to reproduce a broad array of

colors. In some instances, to include at least red, green and blue colors within a pixel area, separate monochromatic LEDs are fabricated at different non-overlapping zones within the pixel area. The existing technology faces challenges to improve the effective illumination area within each pixel when the distance between the adjacent LEDs is determined. On the other hand, when a single LED illumination area is determined, further improving the overall resolution of the LED panel can be a difficult task because LEDs with different colors have to occupy their designated zones within the single pixel.

[0005] Active matrix liquid-crystal displays (LCD) and organic light-emitting diode (OLED) displays combined with thin-film transistor (TFT) technology are becoming increasingly popular in today's commercial electronic devices. These displays are widely used in laptop personal computers, smartphones and personal digital assistants. Millions of pixels together create an image on a display. The TFTs act as switches to individually turn each pixel on and off, rendering the pixel light or dark, which allows for convenient and efficient control of each pixel and of the entire display.

[0006] However, conventional LCD displays suffer from low light efficiency, causing high power consumption and limited battery operation time. While active-matrix organic light-emitting diode (AMOLED) display panels generally consume less power than LCD panels, an AMOLED display panel can still be the dominant power consumer in battery-operated devices. To extend battery life, it is desirable to reduce the power consumption of the display panel.

[0007] Conventional inorganic semiconductor light-emitting diodes (LED) have demonstrated superior light efficiency, which makes active matrix LED displays more desirable for battery operated electronics. Arrays of driver circuitry and lighting-emitting diodes (LEDs) are used to control millions of pixels, rendering images on the display. Both single-color display panels and full-color display panels can be manufactured according to a variety of fabrication methods.

[0008] However, the integration of thousands or even millions of micro LEDs with pixel driver circuit array is quite challenging. Various fabrication methods have been proposed. In one approach, control circuitry is fabricated on one substrate and LEDs are fabricated on a separate substrate. The LEDs are transferred to an intermediate substrate and the original substrate is removed. Then the LEDs on the intermediate substrate are picked and placed one or a few at a time onto the substrate with the control circuitry. However, this fabrication process is inefficient, costly and not reliable. In addition, there are no existing manufacturing tools for mass transferring micro LEDs. Therefore new tools must be developed.

[0009] In another approach, the entire LED array with its original substrate is aligned and bonded to the control circuitry using metal bonding. The substrate on which the LEDs are fabricated remains in the final product, which may cause light cross-talk. Additionally, the thermal mismatch between the two different substrates generates stress at the bonding interface, which can cause reliability issues. Furthermore, multi-color display panels typically require more LEDs and different color LEDs grown on different substrate materials, compared with single-color display panels, thus making the traditional manufacturing process even more complicated and inefficient.

[0010] Display technologies are becoming increasingly popular in today's commercial electronic devices. These display panels are widely used in stationary large screens such as liquid crystal display televisions (LCD TVs) and organic light-emitting diode televisions (OLED TVs) as well as portable electronic devices such as laptop personal computers, smartphones, tablets and wearable electronic devices. Much of development for the stationary large screens is directed to achieve a high viewing angle in order to accommodate and enable multiple audiences to see the screen from various angles. For example, various liquid crystal materials such as super twisted nematic (STN) and film compensated super twisted nematic (FSTN) have been developed to achieve a large viewing angle of each and every pixel light source in a display panel.

[0011] However, most of the portable electronic devices are designed mainly for single users, and screen orientation of these portable devices should be adjusted to be the best viewing angle for the

corresponding users instead of a large viewing angle to accommodate multiple audiences. For example, a suitable viewing angle for a user may be perpendicular to the screen surface. In this case, compared with stationary large screens, light emitted at a large viewing angle is mostly wasted. Additionally, large viewing angles raise privacy concerns for portable electronic devices used in public areas.

[0012] In addition, in a conventional projection system based on a passive imager device, such as liquid crystal display (LCD), digital mirror devices (DMD), and liquid crystal on silicon (LCOS), the passive imager device itself does not emit light. Specifically, the conventional projection system projects images by optically modulating collimated light emitted from a light source, i.e., by either transmitting, e.g., by an LCD panel, or reflecting, e.g., by a DMD panel, part of the light at the pixel level. However, the part of the light that is not transmitted or reflected is lost, which reduces the efficiency of the projection system. Furthermore, to provide the collimated light, complex illumination optics are used to collect divergent light emitted from the light source. The illumination optics not only cause the system to be bulky but also introduce additional optical loss into the system, which further impacts the performance of the system. In a conventional projection system, typically less than 10% of the illumination light generated by the light source is used to form the projection image.

[0013] Light-emitting diodes (LEDs) made of semiconductor materials can be used in mono-color or full-color displays. Current displays that employ LEDs, the LEDs are usually used as the light source to provide the light to be optically modulated by, e.g., the LCD or the DMD panel. That is, the light emitted by the LEDs does not form images by itself. LED displays using LED panels including a plurality of LED dies as the imager devices have also been studied. In such an LED display, the LED panel is a self-emissive imager device, where each pixel can include one LED die (mono-color display) or a plurality of LED dies each of which represents one of primary colors (full-color display).

[0014] However, the light emitted by the LED dies is generated from spontaneous emission and is thus not directional, resulting in a large divergence angle. The large divergence angle can cause various problems in a micro-LED display. On one hand, due to the large divergence angle, only a small portion of the light emitted by the micro-LEDs can be utilized. This may significantly reduce the efficiency and brightness of a micro-LED display system. On the other hand, due to the large divergence angle, the light emitted by one micro-LED pixel may illuminate its adjacent pixels, resulting in light crosstalk between pixels, loss of sharpness, and loss of contrast. Conventional solutions reducing the large divergence angle may not effectively handle the light emitted from the micro-LED as a whole, and may utilize only the central portion of the light emitted from the micro-LED, leaving the rest of the light emitted at more oblique angles to be unutilized.

[0015] As such, it would be desirable to provide an LED structure for display panels that addresses the above-mentioned drawbacks, amongst others.

## SUMMARY

[0016] There is a need for improved multi-color LED designs that improve upon, and help to address the shortcomings of conventional display systems, such as those described above. In particular, there is a need for an LED device structure that can improve the brightness and resolution at the same time while efficiently maintaining low power consumption. And there is also a need for display panels with reduced viewing angle for better protection for user's privacy, or/and reduced light waste for reduced power consumption and reduced light interference between pixels with better images.

[0017] The multi-color LED device described herein integrates at least three micro-LED structures vertically stacked by placing them at different layers of the device structure and utilizing separate electrodes for receiving control currents. By placing at least three LED structures aligned along one axis as disclosed herein, the system effectively enhances the light illumination efficiency within a single pixel area, and at the same time, improves the resolution of the LED panel.

[0018] Pitch refers to the distance between the centers of adjacent pixels on a display panel. In some embodiments, the pitch can vary from about 40 microns, to about 20 microns, to about 10 microns, and/or preferably to about 5 microns or below. Many efforts have been made to reduce the pitch. A single pixel area is fixed when the pitch specification is determined.

[0019] The multi-color coaxial LED system described herein makes it possible to emit light with a combination of different colors from a single pixel area without using extra area to accommodate LED structures with different colors. Therefore, the footprint of a single pixel is significantly reduced and the resolution of the micro-LED panel can be improved. While the concentration of the different-colored light from one micro-LED device boundary greatly enhances the brightness within a single pixel area.

[0020] Compared to conventional fabrication processes for micro-LED display chips, which rely on inefficient pick and place processes or unreliable multiple substrates approaches, the multi-color micro-LED fabrication processes disclosed herein effectively increases the efficiency and reliability of the micro-LED device fabrication. For example, the LED structures can be directly bonded on the substrate with the pixel drivers without introducing an intermediate substrate, which can simplify the fabrication steps and thus enhance the reliability and performance of the LED chip. In addition, no substrate for the micro-LED structures remain in the final multi-color device so that cross-talk and mismatch can be reduced. In addition, planarization is applied to either one of the LED structures within the multi-color micro-LED or applied to the whole multi-color micro-LED, thus allowing direct bonding or formation of different LED structures and/or other layers together with less destruction to the existing structures within the planarized layers.

[0021] The multi-color micro-LED devices described herein can include vertical light emission, e.g., light from each of the stacked LED structures is emitted substantially vertically relative to the surface of a substrate, horizontal light emission, e.g., light from each of the stacked LED structures is emitted substantially or only horizontally relative to the surface of a substrate then reflected substantially vertically by some reflective structures, or any combination thereof. Since vertically emitted light needs to pass through all the different layers within the multi-color micro-LED device, various layers of improving light transmission and light reflection are implemented. Compared with the vertical light emission, light emitted horizontally from each of the stacked LED structures does not need to pass through all the layers above a particular structure. Therefore, horizontal light emission may have better light transmission efficiency and result in better light distinctiveness.

[0022] Various embodiments include a display panel with integrated micro-lens array. The display panel typically includes an array of pixel light sources (e.g., LEDs, OLEDs) electrically coupled to corresponding pixel driver circuits (e.g., FETs). The array of micro-lenses is aligned to the pixel light sources and positioned to reduce the divergence of light produced by the pixel light sources. The display panel may also include an integrated optical spacer to maintain the positioning between the micro-lenses and pixel driver circuits.

[0023] The micro-lens array reduces the divergence angle of light produced by the pixel light sources and the useable viewing angle of the display panel. This, in turn, reduces power waste, increases brightness and/or better protects user privacy in public areas.

[0024] A display panel with integrated micro-lens array can be fabricated using a variety of manufacturing methods, resulting in a variety of device designs. In one aspect, the micro-lens array is fabricated directly as mesas or protrusions of the substrate with the pixel light sources. In some aspects, self-assembly, high temperature reflow, grayscale mask photolithography, molding/imprinting/stamping, and dry etching pattern transfer are techniques that can be used to fabricate micro-lens arrays.

[0025] Other aspects include components, devices, systems, improvements, methods and processes including manufacturing methods, applications, and other technologies related to any of the above.

[0026] Some exemplary embodiments include a reflective cup disposed on the semiconductor

substrate and surrounding the light emitting region, e.g. a region where the light from the multi-color micro-LED device is emitted. The reflective cup can reduce the divergence of the light emitted from the light emitting region, and suppress the light crosstalk between adjacent pixel units. For example, the reflective cup can utilize the light at oblique angles, which is more efficient in collecting and converging this light for high-brightness and power-efficient display than conventional solutions. In addition, the reflective cup can block the light emitting from micro-LEDs in adjacent pixel units, which can effectively suppress the inter-pixel light crosstalk and enhance color contrast and sharpness. Exemplary embodiments of the present disclosures can improve projection brightness and contrast, and therefore reduce power consumption in projection applications. Exemplary embodiments of the present disclosures can also improve the light-emission directionality of the display, and therefore provide user with better image quality and protect user's privacy in direct-view applications. Exemplary embodiments of the present disclosure can provide multiple advantages. One advantage is that exemplary embodiments of the present disclosure can suppress inter-pixel light crosstalk and enhance brightness. Exemplary embodiments of the present disclosure can suppress the inter-pixel light crosstalk at a smaller pitch while enhancing brightness within a single pixel in a power-efficient manner.

[0027] In some exemplary embodiments, the single pixel multi-color LED device may include one or more top electrodes integrated with the reflective cup. The top electrodes may electrically connect with the top electrode layer. The top electrode integration with the reflective cup may make the single pixel multi-color LED device structure more compact and simplify the fabrication process. With the adoption of the top electrodes, the reflective cup can perform as a common P- or N-electrode of the single pixel multi-color LED device, and thus may offer a compact structure of the single pixel multi-color LED device.

[0028] In some exemplary embodiments, the micro-LED-pixel unit may include a micro-lens, in addition to the reflective cup. The micro-lens may be aligned to the light emitting region and positioned to reduce the divergence of the light emitting from the light source and decrease usable viewing angle from the single pixel multi-color LED device. For example, the micro-lens may be co-axially aligned to the light emitting region, and be positioned on the light emitting region as well as top of the reflective cup. Part of the light emitted from the light emitting region can directly arrive at and pass through the micro-lens; and the other part of the light emitted from the light emitting center can arrive at and be reflected by the reflective cup and then arrive at and pass through the micro-lens. Therefore, the divergence can be reduced and the useable viewing angle can be decreased to the extent that displays and panels using the single pixel multi-color LED devices may be seen by one user perpendicular to surfaces of the displays and panels. This, in turn, can reduce power waste and increase brightness and/or better protects user privacy in public areas. In another example, the micro-lens may be co-axially aligned to the light emitting region, positioned on the light emitting and surrounded by the reflective cup. Part of the light emitted from the light emitting region can directly arrive at and pass through the micro-lens; another part of the light emitted from the light emitting center can arrive at and be reflected by the reflective cup and then arrive at and pass through the micro-lens; and the rest of the light emitted from the light emitting center can arrive at and be reflected by the reflective cup without passing through the micro-lens. Therefore, the divergence can be reduced and the useable viewing angle can be decreased to the extent that displays and panels using the single pixel multi-color LED devices may be seen by several users. This can also reduce power waste, increase brightness and/or properly protect user privacy in public areas.

[0029] In some exemplary embodiments, the single pixel multi-color LED device may further include a spacer. The spacer may be an optically transparent layer formed to provide a proper spacing between the micro-lens and the light emitting region. For example, the spacer may be disposed between the micro-lens and the top of the reflective cup, when the micro-lens is disposed above the reflective cup. Thus, the light emitted from the light emitting region can pass through the

spacer and then pass through the micro-lens. The spacer may also fill up the area surrounded by the reflective cup to increase the refractive index of the medium surrounding the light emitting region. Therefore, the spacer can change the optical path of the light emitted from the light emitting region. With the adoption of the micro-lens, the light extraction efficiency of the single pixel multi-color LED device can be increased to further enhance the brightness of, e.g., the micro-LED display panel.

[0030] In some exemplary embodiments, the single pixel multi-color LED device may include a stair-shaped reflective cup. The stair-shaped reflective cup may include a cavity surrounding the light emitting region. The cavity may be formed by a plurality of inclined surfaces surrounding the light emitting region. Sub-cavities may be formed by the plurality of inclined surfaces and may have different dimensions in the horizontal direction. The stair-shaped reflective cup may be disposed on the semiconductor substrate. The stair-shaped reflective cup can reduce the divergence of the light emitted from the light emitting region, and suppress the light crosstalk between adjacent pixel units. For example, the stair-shaped reflective cup can utilize the light at oblique angles by reflecting them in different reflection directions. In addition, the stair-shaped reflective cup can block the light emitting from micro-LEDs in adjacent pixel units, which can effectively suppress the inter-pixel light crosstalk and enhance color contrast and sharpness. Exemplary embodiments of the present disclosures can improve projection brightness and contrast, and therefore reduce power consumption in projection applications. Exemplary embodiments of the present disclosures can also improve the light-emission directionality of the display, and therefore provide user with better image quality and protect user's privacy in direct-view applications.

[0031] The multi-color micro-LED devices described herein can improve brightness and resolution at the same time and are suitable for modern display panels, especially for high definition AR devices and virtual reality (VR) glasses.

[0032] Some exemplary embodiments provide a multi-color micro light-emitting diode (LED) pixel unit for a display panel that includes: a first color LED structure, formed on an IC substrate, wherein the first color LED structure includes a first light emitting layer, and a first reflective structure is formed on a bottom of the first light emitting layer; a first dielectric bonding layer having a flat top surface, covering the first color LED structure; a second color LED structure, formed on the flat top surface of the first dielectric bonding layer, wherein the second color LED structure includes a second light emitting layer, and a second reflective structure is formed on a bottom of the second light emitting layer; a second dielectric bonding layer having a flat top surface, covering the second color LED structure; a top electrode layer, covering the micro-LED pixel unit and electrically contacting with the first color LED structure and the second color LED structure; and, the IC substrate electrically connected with the first color LED structure and the second LED structure.

[0033] Some exemplary embodiments provide a micro-LED pixel unit, that includes: a first color LED structure, formed on an IC substrate, wherein the first color LED structure includes a first light emitting layer, and a first reflective structure is formed on the bottom of the first light emitting layer; a first dielectric bonding layer having a flat top surface, covering the first color LED structure; a second color LED structure, formed on the flat top surface of the first dielectric bonding layer, wherein the second color LED structure includes a second light emitting layer, and a second reflective structure is formed on a bottom of the second light emitting layer; a second dielectric bonding layer having a flat top surface, covering the second color LED structure; a third color LED structure, formed on the flat top surface of the second dielectric bonding layer, wherein the third color LED structure includes a third light emitting layer and, a third reflective structure is formed on the bottom of the third light emitting layer; a third dielectric bonding layer having a flat top surface, covering the third color LED structure; a top electrode layer, covering the micro-LED pixel unit and electrically contacting with the first color LED structure, the second color LED structure and the third color LED structure; and, the IC substrate electrically connected with the

first color LED structure, the second LED structure and the third LED structure.

[0034] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first dielectric bonding layer is transparent and the second dielectric bonding layer is transparent.

[0035] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first reflective structure includes at least one first high reflectivity layer, the second reflective structure includes at least one second high reflectivity layer, and the third reflective structure includes at least one third high reflectivity layer; and, the reflectivity of the first high reflectivity layer, the second high reflectivity layer or the third high reflectivity layer is above 60%.

[0036] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the material of the first high reflectivity layer, the second high reflectivity layer or the third high reflectivity layer is metal selected from one or more of Rh, Al, Ag, and Au.

[0037] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first reflective structure includes at least two first high reflectivity layers which have different refractive indices; the second reflective structure includes at two second high reflectivity layers which have different refractive indices; and, the third reflective structure includes at two third high reflectivity layers which have different refractive indices.

[0038] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit the first reflective structure further includes a first transparent layer on the first high reflectivity layer; the second reflective structure further includes a second transparent layer on the second high reflectivity layer; and, the third reflective structure further includes a second transparent layer on the third high reflectivity layer.

[0039] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first transparent layer is selected from one or more of ITO and SiO.sub.2; the second transparent layer is selected from one or more of ITO and SiO.sub.2; and, the third transparent layer is selected from one or more of ITO and SiO.sub.2.

[0040] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first color LED structure further includes a first bottom electrode conductive contact layer, the second color LED structure further includes a second bottom electrode conductive contact layer, and the third color LED structure further includes a third bottom electrode conductive contact layer; the first bottom electrode conductive contact layer is electrically connected with the IC substrate by a first contact via at a bottom of the first bottom electrode conductive contact layer; the second bottom electrode conductive contact layer is electrically connected with the IC substrate by a second contact via through the first dielectric bonding layer; and, the third bottom electrode conductive contact layer is electrically connected with the IC substrate by a third contact via through the second dielectric layer and the first dielectric bonding layer.

[0041] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first bottom electrode conductive contact layer is transparent, the second bottom electrode conductive contact layer is transparent and the third bottom electrode conductive contact layer is transparent.

[0042] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a first extended portion is extended from one side of the first light emitting layer; a second extended portion is extended from one side of the second light emitting layer; a third extended portion is extended from one side of the second light emitting layer; and, a top contact via connects the first extended portion, the second extended portion and the third extended portion to the top electrode layer through the second dielectric bonding layer and the third dielectric bonding layer.



[0043] Some exemplary embodiments provide a micro-LED pixel unit, that at least includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate; and, a reflective optical isolation structure, formed around the light emitting region, wherein the top of the reflective optical isolation structure is higher than the top of the light emitting region.

[0044] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a micro-lens is above the top of the light emitting region.

[0045] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the top of the reflective optical isolation structure is higher than that of the micro-lens.

[0046] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the reflective optical isolation structure has a top opening, the lateral area of the micro-lens is less than that of the top opening.

[0047] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the lateral dimension of the micro-lens is larger than an active emitting area of the first color LED structure; the lateral dimension of the micro-lens is larger than an active emitting area of the second color LED structure; and, the lateral dimension of the micro-lens is larger than an active emitting area of the third color LED structure.

[0048] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, lateral dimensions of the first color LED structure, the second color LED structure and the third color LED structure are the same.

[0049] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first LED structure, the second LED structure and the third LED structure have a same center axis.

[0050] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first dielectric bonding layer is transparent, the second dielectric bonding layer is transparent, and the third dielectric bonding layer is transparent.

[0051] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a thickness of the first reflective structure is 5 nm to 10 nm; a thickness of the second reflective structure is 5 nm to 10 nm; a thickness of the third reflective structure is 5 nm to 10 nm; a thickness of the first LED structure is not more than 300 nm; a thickness of the second LED structure is not more than 300 nm; and, a thickness of the third LED structure is not more than 300 nm.

[0052] Some exemplary embodiments provide a multi-color micro-LED pixel unit for a display panel that includes: a first LED structure that emits a first color, formed on an IC substrate; a first transparent dielectric bonding layer having a first flat top surface, covering the first LED structure; a second LED structure that emits a second color, formed on the first flat top surface of the first transparent dielectric bonding layer; a second transparent dielectric bonding layer having a second flat top surface, covering the second LED structure; and a top electrode layer, covering the multi-color micro-LED pixel unit and electrically contacting with the first LED structure and the second LED structure; wherein the IC substrate is electrically connected with the first LED structure and the second LED structure.

[0053] Some exemplary embodiments provide a micro-LED pixel unit, that includes: a first color LED structure, formed on an IC substrate; a first transparent dielectric bonding layer having a flat top surface, covering the first color LED structure; a second color LED structure, formed on the flat top surface of the first transparent dielectric bonding layer; a second transparent dielectric bonding layer having a flat top surface, covering the second color LED structure; a third color LED structure, formed on the flat top surface of the second transparent dielectric bonding layer; a third dielectric bonding layer having a flat top surface, covering the third color LED structure; a top electrode layer, covering the micro-LED pixel unit and electrically contacting with the first color LED structure, the second color LED structure and the third color LED structure; and the IC

substrate electrically connected with the first color LED structure, the second LED structure and the third LED structure.

[0054] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a first reflective structure is formed at the bottom of the first color LED structure; a second reflective structure is formed at the bottom of the second color LED structure; and, a third reflective structure is formed at the bottom of the third color LED structure.

[0055] Some exemplary embodiments provide a micro-LED pixel unit, that includes: an IC substrate; a light emitting region, formed on the IC substrate, including at least one kind of LED structure and at least a dielectric bonding layer, wherein each of the dielectric bonding layer have a flat top surface covering a surface of every LED structure; a top electrode layer, covering the micro-LED pixel unit and electrically contacting with the every color LED structure, wherein the IC substrate is electrically connected with every color LED structure; and, a stair-shaped reflective cup structure having a cavity, surrounding the light emitting region.

[0056] Some exemplary embodiments provide a micro-LED pixel unit, that includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate; a reflective optical isolation structure, formed around the light emitting region; and, a refractive structure, formed between the reflective optical isolation structure and the light emitting region.

[0057] Some exemplary embodiments provide a micro-LED pixel unit, that includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate, including at least one kind of LED structure and at least a transparent dielectric bonding layer, wherein each of the transparent dielectric bonding layer having a flat top surface covering a surface of every LED structure; a top electrode layer, covering the micro-LED pixel unit and electrically contacting with every color LED structure, wherein the IC substrate is electrically connected with every color LED structure; a stair-shaped reflective cup structure, formed around the light emitting region; and, a refractive structure, formed between the stair-shaped reflective cup structure and the light emitting region.

[0058] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the reflective cup structure has a top opening, the lateral area of the micro-lens is less than that of the top opening.

[0059] Some exemplary embodiments provide a micro-LED pixel unit that includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate; a floating reflective optical isolation structure, surrounding the light emitting region, wherein the floating reflective optical isolation structure is positioned at a distance above the semiconductor substrate.

[0060] Some exemplary embodiments provide a micro-LED pixel unit, that includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate; a reflective optical isolation structure, surrounding the light emitting region; a top electrode layer, covering the light emitting region and electrically connecting the reflective optical isolation structure, wherein the top electrode layer electrically contacts the reflective optical isolation structure.

[0061] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, an edge of the top electrode layer touches the reflective optical isolation structure.

[0062] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the light emitting region includes: at least one kind of LED structure and at least a dielectric bonding layer; a top electrode layer, covering the micro-LED pixel unit and electrically contacting with every color LED structure, wherein the semiconductor substrate is electrically connected with every color LED structure.

[0063] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the reflective optical isolation structure is a floating reflective structure.

[0064] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the reflective optical isolation structure is a stair-shaped reflective cup structure.

[0065] Some exemplary embodiments provide a micro-LED pixel unit, that at least includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate; a floating reflective optical isolation structure, surrounding the light emitting region, wherein the floating reflective optical isolation structure is positioned at a distance above the semiconductor substrate; and a top electrode layer, formed on top of the light emitting region, wherein the top electrode layer contacts with the floating reflective optical isolation structure.

[0066] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the light emitting region includes at least one kind of LED structure and a bonding layer at the bottom of each LED structure.

[0067] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first color LED structure further includes a first bottom electrode conductive contact layer, the second color LED structure further includes a second bottom electrode conductive contact layer; the first bottom electrode conductive contact layer is electrically connected with the IC substrate by a first contact via at the bottom of the first bottom electrode conductive contact layer; the second bottom electrode conductive contact layer is electrically connected with the IC substrate by a second contact via through the first dielectric bonding layer.

[0068] Some exemplary embodiments provide a micro-LED pixel unit, that includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate; a top electrode layer, covering the light emitting region and electrically contacting with the light emitting region; a reflective cup structure, formed around the light emitting region, wherein the top electrode layer is electrically connected with the reflective cup structure; the semiconductor substrate is electrically connected with the reflective cup structure; and, a refractive structure, formed between the reflective cup structure and the light emitting region.

[0069] Some exemplary embodiments provide a micro-LED pixel unit that includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate, including at least one kind of LED structure and a bonding layer at a bottom of every LED structure, wherein each LED structure includes a light emitting layer and a bottom reflective structure at a bottom of the light emitting layer; a top electrode layer, covering the micro-LED pixel unit and electrically contacting with every color LED structure, wherein the semiconductor substrate is electrically connected with every color LED structure; a reflective cup structure, formed around the light emitting region; and, a refractive structure, formed between the reflective cup structure and the light emitting region.

[0070] Some exemplary embodiments provide a micro-LED pixel unit that includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate, including at least one kind of LED structure and a bonding layer at the bottom of every LED structure, wherein the LED structure includes a light emitting layer and a reflective structure at the bottom of the light emitting layer; a top electrode layer, covering the LED structure pixel unit and electrically contacting with every color LED structure, wherein the semiconductor substrate is electrically connected with every color LED structure; and, a stair-like reflective cup structure, surrounding the light emitting region, the light emitted from the sidewalls of the first light emitting layer and the second light emitting layer along the horizontal level arriving at and being reflected upward by the stair-like reflective cup structure, wherein the top of the stair-like reflective cup structure is higher than the top of the light emitting region.

[0071] Some exemplary embodiments provide a micro-LED pixel unit that includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate, including at least one kind of LED structure and a metal bonding layer at a bottom of every LED structure, wherein the LED structure includes a light emitting layer and a reflective structure at a bottom of

the light emitting layer, a top electrode layer, covering the micro-LED pixel unit and electrically contacting with every color LED structure, wherein the semiconductor substrate is electrically connected with every color LED structure; and, a floating reflective cup structure, surrounding the light emitting region, wherein the floating reflective cup structure is positioned a distance from the semiconductor substrate, the light emitted from the sidewalls of the first light emitting layer and the second light emitting layer along the horizontal level arriving at and being reflected upward by the floating reflective cup.

[0072] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the bottom of the floating reflective cup structure is higher than the top surface of the semiconductor substrate.

[0073] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the floating reflective cup structure is a stair-shaped reflective cup structure.

[0074] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first LED structure is embedded within a first planarized transparent dielectric layer.

[0075] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first planarized transparent dielectric layer is composed of solid inorganic materials or plastic materials.

[0076] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the second LED structure is embedded within a second planarized transparent dielectric layer.

[0077] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the second planarized transparent dielectric layer is composed of solid inorganic materials or plastic materials.

[0078] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first transparent dielectric bonding layer is composed of solid inorganic materials or plastic materials.

[0079] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first LED structure includes a first bottom electrode conductive contact layer formed on the bottom of the first LED structure; the second LED structure includes a second bottom electrode conductive contact layer formed on the bottom of the second LED structure; the first bottom electrode conductive contact layer is electrically connected with the IC substrate by a first contact in a first via at the bottom of the first bottom electrode conductive contact layer; and the second bottom electrode conductive contact layer is electrically connected with the IC substrate by a second contact in a second via through the first transparent dielectric bonding layer.

[0080] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first bottom electrode conductive contact layer is transparent, and the second bottom electrode conductive contact layer is transparent.

[0081] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first LED structure includes a first light emitting layer; a first side portion is extended from a side of the first light emitting layer; the second LED structure includes a second light emitting layer; a second side portion is extended from a side of the second light emitting layer; and a third contact in a third via connects the first side portion and the second side portion to the top electrode layer through the second transparent dielectric bonding layer.

[0082] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, an optical isolation structure is formed around the micro-LED pixel unit.

[0083] In some exemplary embodiments or any combination of preceding exemplary embodiments

of the micro-LED pixel unit, the optical isolation structure is a reflective cup.

[0084] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the lateral dimension of the first LED structure is the same as that of the second LED structure.

[0085] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first LED structure and the second LED structure have a same central axis.

[0086] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a first reflective layer is formed at the bottom of the first LED structure; a second reflective layer is formed at the bottom of the second LED structure.

[0087] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a thickness of the first reflective layer is 5 to 10 nm; a thickness of the second reflective layer is 5 to 10 nm; a thickness of the first LED structure is not more than 300 nm; and, a thickness of the second LED is not more than 300 nm.

[0088] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a bonding metal layer is formed at the bottom of the first LED structure.

[0089] Some exemplary embodiments provide a micro-light LED pixel unit, that includes: a first color LED structure, formed on an IC substrate, wherein the first color LED structure includes a first light emitting layer, and a first reflective structure is formed on a bottom of the first light emitting layer; a first bonding metal layer, formed at a bottom of the first color LED structure, and configured to bond the IC substrate and the first color LED structure; a second bonding metal layer, formed on a top of the first color LED structure; a second color LED structure, formed on the second bonding metal layer, wherein the second color LED structure includes a second light emitting layer, and a second reflective structure is formed on a bottom of the second light emitting layer; a top electrode layer, covering the first color LED structure and the second color LED structure and electrically contacting with the first color LED structure and the second color LED structure, wherein the IC substrate is electrically connected with the first color LED structure and the second color LED structure; and a reflective cup, surrounding the first color LED structure and the second color LED structure, light emitted from the first light emitting layer and the second light emitting layer in a horizontal direction arriving at and being reflected upward by the reflective cup.

[0090] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first reflective structure includes at least one first reflective layer and the second reflective structure includes at least one second reflective layer, reflectivity of the first reflective layer or the second reflective layer being above 60%.

[0091] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the material of the first reflective layer or the second reflective layer comprises one or more of Rh, Al, Ag, or Au.

[0092] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first reflective structure includes two first reflective layers and refractive indices of the two first reflective layers are different, and wherein the second reflective structure includes two second reflective layers and refractive indices of the two second reflective layers are different.

[0093] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the two first reflective layers comprise SiO<sub>2</sub> and Ti<sub>3O<sub>5</sub></sub> respectively, and the two second reflectivity layers comprise SiO<sub>2</sub> and Ti<sub>3O<sub>5</sub></sub> respectively.

[0094] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first reflective structure further includes a first transparent layer on the first reflective layer, and the second reflective structure further includes a second transparent

layer on the second reflective layer.

[0095] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first transparent layer comprises one or more of indium tin oxide (ITO) or SiO<sub>2</sub>, and the second transparent layer comprises one or more of ITO or SiO<sub>2</sub>.

[0096] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first color LED structure further includes a first bottom conductive contact layer and a first top conductive contact layer, and the second color LED structure further includes a second bottom conductive contact layer and a second top conductive contact layer; the first light emitting layer is between the first bottom conductive contact layer and the first top conductive contact layer, and the second light emitting layer is between the second bottom conductive contact layer and the second top conductive contact layer; the first bottom conductive contact layer is electrically connected with the IC substrate through the first reflective structure and the first bonding metal layer through a first contact via, and the second bottom conductive contact layer is electrically connected with the IC substrate through a second contact via; and an edge of the first top conductive contact layer is in contact with the top electrode layer, and a top surface of the second top conductive contact layer is in contact with the top electrode layer.

[0097] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the material of the reflective cup comprises metal.

[0098] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a micro-lens is formed above the top electrode layer.

[0099] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a spacer is formed between the micro-lens and the top electrode layer.

[0100] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the material of the spacer comprises silicon oxide.

[0101] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the lateral dimension of the micro-lens is larger than that of an active emitting area of the first LED structure; and the lateral dimension of the micro-lens is larger than that of an active emitting area of the second LED structure.

[0102] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first color LED structure and the second color LED structure have a same lateral dimension.

[0103] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the first color LED structure and the second color LED structure have a same center axis.

[0104] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a thickness of the at least one first reflective layer is in a range of 5 nm to 10 nm, and a thickness of the at least one second reflective layer is in a range of 5 nm to 10 nm, and wherein a thickness of the first color LED structure is not more than 300 nm, and a thickness of the second color LED structure is not more than 300 nm.

[0105] Some exemplary embodiments provide a micro-LED pixel unit that includes: an IC substrate; a light emitting region, formed on the IC substrate, including a plurality of color LED structures, a bottom of each of the plurality of color LED structures being connected to a corresponding bonding metal layer in the light emitting region, wherein each of the plurality of color LED structures includes a light emitting layer and a reflective structure at a bottom of the light emitting layer; a top electrode layer, covering each of the plurality of color LED structures and electrically contacting to each of the plurality of color LED structures, wherein the IC substrate is electrically connected with each of the plurality of color LED structures; and, a stair-shaped reflective cup forming a cavity, surrounding the light emitting region, light emitted from sidewalls of the light emitting layer of each of the plurality of color LED structures in a horizontal direction arriving at and being reflected upward by the reflective cup.

[0106] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, an inner sidewall of the cavity includes a plurality of inclined surfaces.

[0107] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, angles of the plurality of inclined surfaces relative to surface of the IC substrate from bottom to top of the cavity become smaller.

[0108] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, sub-cavities formed by the plurality of inclined surfaces have different dimensions in the horizontal direction.

[0109] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, inner sidewalls of the sub-cavities are not arranged in a same plane.

[0110] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the heights of the sub-cavities are different.

[0111] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the height of a sub-cavity in middle of the cavity is less than the heights of other sub-cavities.

[0112] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the height of a sub-cavity at top of the cavity is larger than the height of a sub-cavity at the bottom of the cavity.

[0113] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the plurality of color LED structures further includes a top color LED structure.

[0114] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the top of the cavity is higher than the top of the top color LED structure.

[0115] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the cavity includes a plurality of sub-cavities, and each of the plurality of color LED structures is in a respectively different one of the sub-cavities.

[0116] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a transparent dielectric bonding layer covers at least one of the plurality of color LED structures, wherein the transparent dielectric bonding layer comprises solid inorganic materials or plastic materials.

[0117] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the solid inorganic materials comprise one or more materials selected from the group consisting of  $\text{SiO}_2$ ,  $\text{Al}_2\text{O}_3$ ,  $\text{Si}_3\text{N}_4$ , Phosphosilicate glass (PSG), and Borophosphosilicate glass (BPSG).

[0118] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the plastic materials comprise one or more polymers selected from the group consisting of SU-8, PermiNex, Benzocyclobutene (BCB), and spin-on glass (SOG).

[0119] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, each of the plurality of color LED structures includes a bottom conductive contact layer and a top conductive contact layer, and the light emitting layer is formed between the bottom conductive contact layer and the top conductive contact layer; and wherein the bottom conductive contact layer is electrically connected with the IC substrate through the reflective structure and the corresponding bonding metal layer through a contact via, and, a top surface of the top conductive contact layer of the top color LED structure is in contact with the top electrode layer, and an edge of the top conductive contact layer of a color LED structure under the top color LED structure is in contact with the top electrode layer.

[0120] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, an extended portion is extended from one side of the light emitting

layer of a color LED structure under the top color LED structure, a contact via connecting the extended portion to the top electrode layer.

[0121] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the lateral dimension of the micro-lens is larger than a light emitting dimension of each of the plurality of color LED structures.

[0122] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the plurality of color LED structures have a same center axis.

[0123] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the reflective structure includes a reflective layer and a thickness of the reflective layer is in a range of 5 nm to 10 nm, and a thickness of each of the plurality of color LED structures is not more than 300 nm.

[0124] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the material of the top electrode layer is selected from the group consisting of graphene, Indium tin oxide (ITO), Aluminum-Doped Zinc Oxide (AZO), and Fluorine doped Tin Oxide (FTO).

[0125] Some exemplary embodiments provide a micro-LED pixel unit, that includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate, including a plurality of color LED structures, a bottom of each of the plurality of color LED structures being connected to a corresponding bonding metal layer in the light emitting region, wherein each of the plurality of color LED structure includes a light emitting layer and a reflective structure at a bottom of the light emitting layer; a top electrode layer, covering each of the plurality of color LED structures and electrically contacting with each of the plurality of color LED structures, wherein the semiconductor substrate is electrically connected with each of the plurality of color LED structures; a reflective cup, surrounding the light emitting region; and a refractive structure, formed between the reflective cup and the light emitting region.

[0126] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a micro-lens is formed on a top surface of the refractive structure.

[0127] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the lateral dimension of the micro-lens is not less than the lateral dimension of the light emitting region.

[0128] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the reflective cup has a top opening area, and the lateral dimension of the micro-lens is less than the lateral dimension of the top opening area.

[0129] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a bottom dielectric layer is formed between the bottom of the reflective cup and the semiconductor substrate.

[0130] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a top conductive layer formed on the top of the light emitting region, and the top conductive layer is electrically connected with the reflective cup.

[0131] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the top conductive layer directly contacts with the top of the reflective cup or the bottom of the reflective cup.

[0132] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the top of the refractive structure is higher than the top of the reflective cup.

[0133] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the semiconductor substrate is an IC substrate.

[0134] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the reflective cup is a stair-shaped reflective cup forming a cavity encompassing the light emitting region.



[0135] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, sub-cavities formed by the plurality of inclined surfaces have different dimensions in the horizontal direction.

[0136] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, each of the plurality of color LED structures includes a respective extended portion extended from one side of the respective color LED structure, and the respective extended portion is electrically connected with the top electrode layer via a respective first contact via, and the bottom of each of the plurality of color LED structures is electrically connected with the semiconductor substrate via a respective second contact via.

[0137] Some exemplary embodiments provide a micro-LED pixel unit, that includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate, including a plurality of color LED structures, a bottom of each of the plurality of color LED structures being connected to a corresponding bonding metal layer in the light emitting region, wherein each of the plurality of color LED structures includes a light emitting layer and a reflective structure at a bottom of the light emitting layer; a top electrode layer, covering each of the plurality of color LED structures and electrically contacting with each of the plurality of color LED structures, wherein the semiconductor substrate is electrically connected with each of the plurality of color LED structures; and, a reflective cup, surrounding the light emitting region, light emitted from sidewalls of the light emitting layer of each of the plurality of color LED structures in a horizontal direction arriving at and being reflected upward by the reflective cup, a top of the reflective cup being higher than a top of the light emitting region.

[0138] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a micro-lens is formed above the light emitting region.

[0139] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the top of the reflective cup is higher than a top of the micro-lens.

[0140] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a refractive structure is at the bottom of the micro-lens and formed between the reflective cup and the light emitting region.

[0141] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the bottom of the light emitting region is electrically connected with the semiconductor substrate.

[0142] Some exemplary embodiments provide a micro-LED pixel unit, that includes: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate, including a plurality of color LED structures, a bottom of each of the plurality of color LED structures being connected to a corresponding bonding metal layer in the light emitting region, wherein each of the plurality of color LED structures includes a light emitting layer and a reflective structure at a bottom of the light emitting layer; a top electrode layer, covering each of the plurality of color LED structures and electrically contacting with each of the plurality of color LED structures, wherein the semiconductor substrate is electrically connected with each of the plurality of color LED structures; and, a floating reflective cup, surrounding the light emitting region, wherein a bottom of the floating reflective cup is above the semiconductor substrate, light emitted from sidewalls of the light emitting layer of each of the plurality of color LED structures in a horizontal direction arriving at and being reflected upward by the suspended floating reflective cup.

[0143] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the bottom of the floating reflective cup is higher than a top surface of the corresponding bonding metal layer at the bottom of one of the plurality of color LED structures.

[0144] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the floating reflective cup is stair-shaped.

[0145] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the top of the floating reflective cup is higher than the top of the

micro-lens.

[0146] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a refractive structure is at the bottom of the micro-lens and formed between the floating reflective cup and the light emitting region.

[0147] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the floating reflective cup has a top opening area, and the lateral dimension of the micro-lens is less than the lateral dimension of the top opening area.

[0148] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a bottom dielectric layer is formed between the floating reflective cup and the semiconductor substrate.

[0149] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the top electrode layer directly contacts the top of the floating reflective cup or the bottom of the floating reflective cup.

[0150] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the stair-shaped floating reflective cup forms a cavity encompassing the light emitting region.

[0151] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the material of the floating reflective cup comprises metal.

[0152] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, the reflective structure includes a reflective layer formed at the bottom of each of the plurality of color LED structures respectively.

[0153] In some exemplary embodiments or any combination of preceding exemplary embodiments of the micro-LED pixel unit, a thickness of the reflective layer is in a range of 5 nm to 10 nm, and a thickness of each of the plurality of color LED structures is not more than 300 nm.

[0154] The compact design of the multi-color LED devices and systems disclosed herein utilizes the lateral overlapping of the light emission LED structures, thereby improving the light emission efficiency, resolution, and overall performance of the LED display systems. Furthermore, the fabrication of the multi-color LED display systems can reliably and efficiently form the LED structure patterns without using or retaining extra substrates. In some instances, the design of the display devices and systems disclosed herein utilizes the direct formation of the micro-lens on top of the multi-color LED devices on the substrate by utilizing the conformity of the shape of the micro-lens material to the shape of the multi-color LED device, thereby greatly reducing the steps of the micro-lens fabrication and improving the efficiency of the display panel structure formation. Reduced viewing angle and reduced light interference improve the light emission efficiency, resolution, and overall performance of the display systems. Thus, implementation of the multi-color LED display systems can satisfy the rigorous display requirements for AR and VR, HUD, mobile device displays, wearable device displays, high definition small projectors, and automotive displays compared with the use of the conventional LEDs.

[0155] Note that the various embodiments described above can be combined with any other embodiments described herein. The features and advantages described in the specification are not all inclusive and, in particular, many additional features and advantages will be apparent to one of ordinary skill in the art in view of the drawings, specification, and claims. Moreover, it should be noted that the language used in the specification has been principally selected for readability and instructional purposes, and may not have been selected to delineate or circumscribe the inventive subject matter.

---

## Description

## BRIEF DESCRIPTION OF THE DRAWINGS

[0156] So that the present disclosure can be understood in greater detail, a more particular description may be had by reference to the features of various embodiments, some of which are illustrated in the appended drawings. The appended drawings, however, merely illustrate pertinent features of the present disclosure and are therefore not to be considered limiting, for the description may admit to other effective features.

[0157] FIG. 1A is a top view of a single pixel tri-color LED device **100**, in accordance with some embodiments.

[0158] FIG. 1B is a cross-sectional view of a single pixel tri-color LED device **100** along the diagonal line **102** in FIG. 1A, in accordance with some embodiments.

[0159] FIG. 1C is a cross-sectional view of a single pixel tri-color LED device **100** along the diagonal line **150** in FIG. 1A, in accordance with some embodiments.

[0160] FIG. 2A is a cross-sectional view of a single pixel tri-color LED device **100** along the diagonal line **102** in FIG. 1A with planarization, in accordance with some embodiments.

[0161] FIG. 2B is a cross-sectional view of a single pixel tri-color LED device **100** along the diagonal line **150** in FIG. 1A with planarization, in accordance with some embodiments.

[0162] FIG. 3A is a cross-sectional view of a single pixel tri-color LED device **100** with planarization along the diagonal line **102** in FIG. 1A with planarization, in accordance with some embodiments.

[0163] FIG. 3B is a cross-sectional view of a single pixel tri-color LED device **100** along the diagonal line **150** in FIG. 1A with planarization, in accordance with some embodiments.

[0164] FIG. 4A is a top view of a single pixel tri-color LED device **400** with layered planarization, in accordance with some embodiments.

[0165] FIG. 4B is a cross-sectional view of a single pixel tri-color LED device **400** along the diagonal line **402** in FIG. 4A with layered planarization, in accordance with some embodiments.

[0166] FIG. 5 is a cross-sectional view of a single pixel tri-color LED device **500** along the diagonal line **102** in FIG. 1A with a refractive structure, in accordance with some embodiments.

[0167] FIG. 6A is a cross-sectional view of a single pixel tri-color LED device **600** along the diagonal line **102** in FIG. 1A with a micro-lens above a reflective structure, in accordance with some embodiments.

[0168] FIG. 6B is a cross-sectional view of a single pixel tri-color LED device **600** along the diagonal line **102** in FIG. 1A with a micro-lens within the area formed by a reflective structure, in accordance with some embodiments.

[0169] FIG. 6C illustrates a fabrication method to form a display panel integrated with a micro-lens array using top down pattern transfer, according to some embodiments.

[0170] FIG. 6D illustrates a fabrication method to form a display panel integrated with a micro-lens array using top down pattern transfer, according to some embodiments.

[0171] FIG. 7 is a cross-sectional view **700** of three single pixel tri-color LED devices **710**, **720** and **730** along the diagonal line such as **102** in FIG. 1A on a substrate **104**, in accordance with some embodiments.

[0172] FIG. 8 is a cross-sectional view of a single pixel tri-color LED device **800** with a stair-shaped reflective cup, along the diagonal line such as **402** in FIG. 4A, in accordance with some embodiments.

[0173] FIG. 9 is a cross-sectional view of a single pixel tri-color LED device **900** with a floating reflective cup, along the diagonal line such as **402** in FIG. 4A, in accordance with some embodiments.

[0174] FIG. 10A is a circuit diagram illustrating a matrix of single pixel tri-color LED devices **1000**, in accordance with some embodiments.

[0175] FIG. 10B is a circuit diagram illustrating a matrix of single pixel tri-color LED devices

**1000**, in accordance with some embodiments.

[0176] FIG. **11** is a top view of a micro LED display panel **1100**, in accordance with some embodiments.

[0177] In accordance with common practice, the various features illustrated in the drawings may not be drawn to scale. Accordingly, the dimensions of the various features may be arbitrarily expanded or reduced for clarity. In addition, some of the drawings may not depict all of the components of a given system, method or device. Finally, like reference numerals may be used to denote like features throughout the specification and figures.

#### DETAILED DESCRIPTION

[0178] Numerous details are described herein in order to provide a thorough understanding of the example embodiments illustrated in the accompanying drawings. However, some embodiments may be practiced without many of the specific details, and the scope of the claims is only limited by those features and aspects specifically recited in the claims. Furthermore, well-known processes, components, and materials have not been described in exhaustive detail so as not to unnecessarily obscure pertinent aspects of the embodiments described herein.

[0179] In some embodiments, a single pixel multi-color LED device includes two or more LED structures. In some embodiments, each of the LED structures includes at least a LED light emitting layer that emits a distinct color. When two LED structures are within a single pixel multi-color LED device, two colors and the combinations of the two colors can be emitted from the single pixel multi-color LED device. When three LED structures are within a single pixel multi-color LED device, three colors and the combinations of the three colors can be emitted from the single pixel multi-color LED device.

[0180] In some embodiments, the light emitted from the single pixel multi-color LED device is from the side walls of each of the LED structures within the single pixel multi-color LED device. In some embodiments, reflective structures positioned surrounding the single pixel multi-color LED device to direct the light from the side walls of each of the LED structures upward. In some embodiments, the light emitted from the single pixel multi-color LED device is from the top surfaces of each of the LED structures within the single pixel multi-color LED device. In some embodiments, the light emitted from the single pixel multi-color LED device is from a combination of the side walls and top surfaces of each of the LED structures within the single pixel multi-color LED device, for example, in a certain ratio, light from the side walls accounts for around 20% to 100% of the light from the single pixel multi-color LED device.

[0181] FIG. **1A** is a top view of a single pixel tri-color LED device **100**, in accordance with some embodiments.

[0182] FIG. **1B** is a cross-sectional view of a single pixel tri-color LED device **100** along the diagonal line **102** in FIG. **1A**, in accordance with some embodiments.

[0183] FIG. **1C** is a cross-sectional view of a single pixel tri-color LED device **100** along the diagonal line **150** in FIG. **1A**, in accordance with some embodiments.

[0184] The diagonal lines **102** and **150** each pass through the center of the single pixel tri-color LED device **100**. The diagonal lines **102** and **150** are orthogonal to each other. In some embodiments, the tri-color LED device **100** includes a substrate **104**. For convenience, “up” is used to mean away from the substrate **104**, “down” means toward the substrate **104**, and other directional terms such as top, bottom, above, below, under, beneath, etc. are interpreted accordingly. The supporting substrate **104** is the substrate on which the array of individual driver circuits **106** is fabricated. In some embodiments, the driver circuits could also be located in one of the layers above the substrate **104**, or above the micro tri-color LED structure **100**. Each driver circuit is a pixel driver **106**. In some instances, the driver circuits **106** are thin-film transistor pixel drivers or silicon CMOS pixel drivers. In one embodiment, the substrate **104** is a Si substrate. In another embodiment, the supporting substrate **104** is a transparent substrate, for example, a glass substrate. Other example substrates include GaAs, GaP, InP, SiC, ZnO, and sapphire substrates. The

driver circuits **106** form individual pixel drivers to control the operation of the individual single pixel tri-color LED device **100**. The circuitry on substrate **104** includes contacts to each individual driver circuit **106** and also a ground contact. As shown in both FIGS. **1A**, **1B** and **1C**, each micro tri-color LED structure **100** also has two types of contacts: P-electrodes or anodes, such as **108**, **126**, **152**, which are connected to the pixel driver **106**; and N-electrodes or cathodes, such as **116**, **120** and **140**, which are connected to the ground (i.e., the common electrode).

[0185] In some embodiments, the N-electrode (or N-electrodes contact pad) and its connections, such as **116**, **120** and **140**, are made of materials such as graphene, ITO, Aluminum-Doped Zinc Oxide (AZO), or Fluorine doped Tin Oxide (FTO), or any combinations thereof. In some embodiments, the N-electrode (or N-electrodes contact pad) and its connections, such as **116**, **120** and **140**, are made of non-transparent or transparent conductive materials and in a preferred embodiment, transparent conductive materials. In some embodiments, the P-electrode (or P-electrodes contact pad) and its connections, such as **126**, **152**, are made of materials such as graphene, ITO, AZO, or FTO, or any combinations thereof. In some embodiments, the P-electrode (or P-electrodes contact pad) and its connections, such as **126**, **152**, are made of non-transparent or transparent conductive materials and in a preferred embodiment, transparent conductive materials. In some embodiments, the locations of the P-electrodes (or P-electrodes contact pad) and its connections, and N-electrodes (or N-electrodes contact pad) and its connections can be switched.

[0186] Although some features are described herein with the term “layer”, it should be understood that such features are not limited to a single layer but may include a plurality of sublayers. In some instance, a “structure” can take the form of a “layer”.

[0187] In some embodiments, three LED structures including LED light emitting layers **112**, **130**, and **136**, respectively, are formed in a stacked structure, for example, a green LED light emitting layer **130** is formed on top of a red LED light emitting layer **112**, and a blue LED light emitting layer **136** is formed on top of the green LED light emitting layer **130**.

[0188] In general, an LED light emitting layer includes a PN junction with a p-type region/layer and an n-type region/layer, and an active layer between the p-type region/layer and n-type region/layer.

[0189] In some embodiments, as shown in FIGS. **1A** and **1B**, the area of the bottom red LED light emitting layer **112** is greater than the area of the middle green LED light emitting layer **130**. In some embodiments, the area of the middle green LED light emitting layer **130** is greater than the area of the top blue LED light emitting layer **136**.

[0190] In some embodiments, the light emitted from the red LED light emitting layer **112** is able to horizontally propagate toward the sidewall of the red LED light emitting layer **112**, then is reflected upward by a reflective element, such as **146** and/or **148**, as described below and emitted out at the top surface of the single pixel tri-color LED device **100**. As described below, a reflective layer **109** is positioned below the red LED light emitting layer **112** and a reflective layer **115** is positioned above the red LED light emitting layer **112**. The light emitted from the red LED light emitting layer **112** is reflected between the two reflective layers **109** and **115** toward the sidewall of the red LED light emitting layer **112**.

[0191] In some embodiments, the light emitted from the green LED light emitting layer **130** is able to horizontally propagate toward the sidewall of the green LED light emitting layer **130**, then is reflected upward by a reflective element, such as **146** and/or **148**, as described below and emitted out at the top surface of the single pixel tri-color LED device **100**. As described below, a reflective layer **127** is positioned below the green LED light emitting layer **130** and a reflective layer **133** is positioned above the green LED light emitting layer **130**. The light emitted from the green LED light emitting layer **130** is reflected between the two reflective layers **127** and **133** toward the sidewall of the green LED light emitting layer **130**.

[0192] In some embodiments, the light emitted from the blue LED light emitting layer **136** is able to horizontally propagate toward the sidewall of the blue LED light emitting layer **136**, then is

reflected upward by a reflective element, such as **146** and/or **148**, as described below and emitted out at the top surface of the single pixel tri-color LED device **100**. As described below, a reflective layer **135** is positioned below the blue LED light emitting layer **136**. The light emitted from the blue LED light emitting layer **136** is reflected between the reflective layer **135** and the upper surface of the blue LED light emitting layer **136** toward the sidewall of the blue LED light emitting layer **136**.

[0193] In some embodiments, the light emitted from the red LED light emitting layer **112** is able to propagate vertically through the green LED light emitting layer **130** and then through the blue LED light emitting layer **136** to be emitted out of the tri-color LED device **100**. In some embodiments, the light emitted from the green LED light emitting layer **130** is able to propagate through the blue LED light emitting layer **136** to be emitted out of the tri-color LED device **100**. In the case of vertical light transmission, in some embodiments, the top reflective layers above each of the light emitting layers, such as **115** and **133**, are preferably not included in the tri-color LED device **100**. In some embodiments, light may be emitted both horizontally and vertically within the different LED light emitting layers.

[0194] In some embodiments, an LED light emitting layer such as **112**, **130**, and **136** includes many epitaxial sub-layers with different compositions. Examples of the LED epitaxial layers include III-V nitride, III-V arsenide, III-V phosphide, and III-V antimonide epitaxial structures. Examples of micro LEDs include GaN based UV/blue/green micro LEDs, AlInGaP based red/orange micro LEDs, and GaAs or InP based infrared (IR) micro LEDs.

[0195] In some embodiments, each of the stacked LED structures can be controlled individually to generate its individual light. In some embodiments, the combined light from the top LED epitaxial layer as a result from the operations all the LED epitaxial layers in the tri-color LED device **100** can change the color of the single pixel on a display panel within a small footprint.

[0196] In some embodiments, depending on the design of the LED device **100**, the emitted colors of the LED structures included in the same device are not limited to red, green and blue. For example, suitable colors can be selected from a range of different colors from a wavelength of 380 nm to 700 nm in visible color range. In some embodiments, LED structures emitting other colors from invisible range such as ultra-violet and infrared can be implemented.

[0197] In some embodiments, when vertical light emission is combined with horizontal light emission, for example, the three-color choice, from bottom to top can be red, green, and blue. In another embodiment, the three-color choice, from bottom to top can be infrared, orange, and ultra-violet. In some embodiments, the wavelength of the light from the LED structure on one layer of the device **100** is longer than the wavelength from the LED structure on a layer on top of the current layer. For instance, the wavelength of the light from the bottom LED light emitting layer **112** is longer than that of the middle LED light emitting layer **130**, and the wavelength of the light from the middle LED light emitting layer **130** is longer than that of the top LED light emitting layer **136**.

[0198] In some embodiments, when in a horizontal light emission case or when the portion of horizontal light emission is more than the portion of vertical light emission from the top surface of the LED device **100**, each of the LED light emitting layers **112**, **130** and **136** can be any suitable visible or invisible color. The advantage of the horizontal light emission is that since the light emitted does not need to go through the other top layers of the LED device **100** but from the edge or sidewall of the current light emitting layer directly, less light transmission loss and higher light emission efficiency can be achieved. For example, compared with the vertical light emission LED device, the horizontal light emission LED device may get 15% more, 50% more, 100% more, 150% more, or 200% more light transmission efficiency. In some instances, the light transmission efficiency from a horizontal light emission LED device can be equal to or greater than 20%, 40% or 60%.

[0199] In some embodiments, the bottom red LED light emitting layer **112** is bonded to the

substrate **104** through a metal bonding layer **108**. The metal bonding layer **108** may be disposed on the substrate **104**. In one approach, a metal bonding layer **108** is grown on the substrate **104**. In some embodiments, the metal bonding layer **108** is electrically connected to both the driver circuit **106** on the substrate **104** and the red LED light emitting layer **112** above the metal bonding layer **108**, acting like a P-electrode. In some embodiments, the thickness of the metal bonding layer **108** is about 0.1 micron to about 3 microns. In a preferred embodiment, the thickness of a metal bonding layer **108** is about 0.3  $\mu\text{m}$ . The metal bonding layer **108** may include ohmic contact layers, and metal bonding layers. In some instances, two metal layers are included in the metal bonding layer **108**. One of the metal layers is deposited the layer above the metal bonding layer within the LED device **100**. A counterpart bonding metal layer is also deposited on the substrate **104**. In some embodiments, compositions for the metal bonding layer **108** include Au—Au bonding, Au—Sn bonding, Au—In bonding, Ti—Ti bonding, Cu—Cu bonding, or a mixture thereof. For example, if Au—Au bonding is selected, the two layers of Au respectively need a Cr coating as an adhesive layer, and Pt coating as an anti-diffusion layer. And the Pt coating is between the Au layer and the Cr layer. The Cr and Pt layers are positioned on the top and bottom of the two bonded Au layers. In some embodiments, when the thicknesses of the two Au layers are about the same, under a high pressure and a high temperature, the mutual diffusion of Au on both layers bond the two layers together. Eutectic bonding, thermal compression bonding, and transient liquid phase (TLP) bonding are example techniques that may be used.

[0200] In some embodiments, the metal bonding layer **108** can also be used as a reflector to reflect light emitted from the LED structures above.

[0201] In some embodiments, a conductive layer **110** for electrode connection is formed at the bottom of the red LED light emitting layer **112**. In some embodiments, the conductive layer **110** can be a non-transparent metal layer which is not transparent to the light emitting from the LED device **100**. In some embodiments, the conductive layer **110** is a conductive transparent layer, which is transparent to the light emitted from the LED device **100**, such as an Indium tin oxide (ITO) layer, that is formed between the red LED light emitting layer **112** and the metal bonding layer **108** to improve conductivity and transparency.

[0202] In some embodiments, not shown in FIG. 1A to 1C, the red LED structure has a P-electrode contact pad **168** electrically connected to the red LED light emitting layer **112**. In some embodiments, the P-electrode contact pad **168** is connected to the conductive layer **110**. In some embodiments, a conductive layer **114** for electrode connection is formed at the top of the red LED light emitting layer **112**. In some embodiments, the conductive layer **114** can be a metal layer or a conductive transparent layer, such as an ITO layer, that is formed between the red LED light emitting layer **112** and an N-electrode contact pad **116** as shown in FIG. 1C to improve conductivity and transparency. In some embodiments, the N-electrode contract pad, such as **116** is made of materials such as graphene, ITO, AZO, or FTO, or any combinations thereof.

[0203] In some embodiments, a reflective layer **109** is positioned below the red LED light emitting layer **112** between the conductive layer **110** and the metal bonding layer **108**, and a reflective layer **115** is positioned above the red LED light emitting layer **112** between the conductive layer **114** and a bonding layer **156**.

[0204] In some embodiments, the red LED light emitting layer **112** has an extended portion **164** at one side of the red LED light emitting layer **112** relative to the layers above it as shown in FIG. 1C. In some embodiments, the extended portion **164** is extended together with the conductive layers **110** and **114**. In some embodiments, the extended portion **164** is extended together with the reflective layer **109** at the bottom of the red LED light emitting layer **112** and the metal bonding layer **108**. In some embodiments, the red LED light emitting layer **112** is connected to the N-electrode contact pad **116** through the extended portion of the conductive layer **114** above the extended portion **164**.

[0205] In one approach, the red LED light emitting layer **112** is grown on a separate substrate

(referred to as the epitaxy substrate). The epitaxy substrate is then removed after bonding, for example, by a laser lift-off process or wet chemical etching, leaving the structure shown in FIGS. 1B and 1C.

[0206] In some embodiments, the red LED light emitting layer **112** is for forming red micro LEDs. Examples of a red LED light emitting layer include III-V nitride, III-V arsenide, III-V phosphide, and III-V antimonide epitaxial structures. In some instances, films within the red LED light emitting layer **112** can include the layers of P-type GaP/P-type AlGaInP light-emitting layer/AlGaInP/N-type AlGaInP/N-type GaAs. In some embodiments, P type layer is generally Mg-doped, and N-type layer is generally Si-doped. In some examples, the thickness of the red LED light emitting layer is about 0.1 micron to about 5 microns. In a preferred embodiment, the thickness of the red LED light emitting layer is about 0.3 micron.

[0207] In some embodiments, the red LED structure includes the metal bonding layer **108**, the reflective layer **109**, the conductive layer **110**, the red LED light emitting layer **112**, the conductive layer **114**, the reflective layer **115**, and the N-electrode contact pad **116**.

[0208] In some embodiments, the bonding layer **156**, is used to bond the red LED structure and the green LED structure together. In some embodiments, the bonding layer **156** is not transparent to the light emitted from the LED device **100**. In some embodiments, the materials and the thickness of the bonding layer **156** is the same as described above for the metal bonding layer **108**. In some embodiments, the bonding layer **156** can also be used as a reflector to reflect light emitted from the LED structures above.

[0209] In some embodiments, when vertical transmission is used, the bonding layer **156** is transparent to the light emitted from the micro LED **100**. In some embodiments, the bonding layer **156** is made of dielectric materials such as solid inorganic materials or plastic materials. In some embodiments, the solid inorganic materials include SiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, Si<sub>3</sub>N<sub>4</sub>, Phosphosilicate glass (PSG), or Borophosphosilicate glass (BPSG), or any combination thereof. In some embodiments, the plastic materials include polymers such as SU-8, PermiNex, Benzocyclobutene (BCB), or transparent plastic (resin) including spin-on glass (SOG), or bonding adhesive Micro Resist BCL-1200, or any combination thereof. In some embodiments, the transparent bonding layers can facilitate the light emitted from the layers below the bonding layers to pass through.

[0210] In some embodiments, as shown in both FIG. 1A and in FIG. 1B, the green LED structures has a P-electrode contact pad **126** electrically connected to the green LED light emitting layer **130**. In some embodiments, the P-electrode contact pad **126** is connected to a conductive layer **128**. In some embodiments, the conductive layer **128** for electrode connection is formed at the bottom of the green LED light emitting layer **130**. In some embodiments, the conductive layer **128** can be a metal layer or a conductive transparent layer, such as an ITO layer, that is formed between the green LED light emitting layer **130** and a P-electrode contact pad **126** as shown in FIGS. 1A and 1B to improve conductivity and transparency.

[0211] In some embodiments, the conductive layer **128** has an extended portion **128-1** at one side of the conductive layer **128** relative to the layers above it as shown in FIG. 1B. In some embodiments, the extended portion **128-1** is extended together with all the layers below the conductive layer **128** within the LED device **100**. In some embodiments, the green LED light emitting layer **130** is electrically connected to the P-electrode contact pad **126** through the extended portion **128-1** of the conductive layer **128**. In some embodiments, the P-electrode contact pad **126** is also electrically connected to the driver circuit **106** in the substrate **104**.

[0212] In some embodiments, an insulation layer **174** made of dielectric materials, such as a SiO<sub>2</sub> layer, is deposited on the surface of the LED device **100**. The P-electrode contact pad **126** is extended from its contact with the driver circuit **106** to its contact with the conductive layer **128** through a via or passage within the insulation layer **174**. The P-electrode contact pad **126** does not contact with other layers within the LED device **100**.

[0213] In some embodiments, a conductive layer **132** for electrode connection is formed at the top



of the green LED light emitting layer **130**. In some embodiments, the conductive layer **132** can be a metal layer or a conductive transparent layer, such as an ITO layer, that is formed between the green LED light emitting layer **130** and an N-electrode contact pad **120** to improve conductivity and transparency. In some embodiments, the N-electrode contact pad **120** is made of transparent conductive materials such as ITO. In some embodiments, the N-electrode contact pad **120** is made of materials such as graphene, ITO, AZO, or FTO, or any combinations thereof.

[0214] In some embodiments, shown in FIG. **1C**, the green LED structure has the N-electrode contact pad **120** electrically connected to the green LED light emitting layer **130**. In some embodiments, the N-electrode contact pad **120** is connected to the conductive layer **132**. In some embodiments, the N-electrode contact pad **120** of the green LED structure is also electrically connected to the N-electrode contact pad **116** of the red LED structure.

[0215] As shown in FIG. **1C**, in some embodiments, the green LED light emitting layer **130** has an extended portion **166** at one side of the green LED light emitting layer **130**. In some embodiments, the extended portion **166** is extended together with the conductive layers **128** and **132** and all other layers below the conductive layer **128**. In some embodiments, the extended portion **166** is electrically connected to the N-electrode contact pad **120** through the extended portion of the conductive layer **132** above the extended portion **166**.

[0216] In some embodiments, the lateral dimension of the green LED light emitting layer **130** is smaller than the lateral dimension of the red LED light emitting layer **112**.

[0217] In some embodiments, a reflective layer **127** is positioned below the green LED light emitting layer **130** between the conductive layer **128** and the bonding layer **156**, and a reflective layer **133** is positioned above the green LED light emitting layer **130** between the conductive layer **132** and a bonding layer **160**.

[0218] In one approach, the green LED light emitting layer **130** is grown on a separate substrate (referred to as the epitaxy substrate). The epitaxy substrate is then removed after bonding, for example, by a laser lift-off process or wet chemical etching, leaving the structure shown in FIGS. **1B** and **1C**.

[0219] In some embodiments, the green LED light emitting layer **130** is for forming green micro LEDs. Examples of a green LED light emitting layer include III-V nitride, III-V arsenide, III-V phosphide, and III-V antimonide epitaxial structures. In some instances, films within the green LED light emitting layer **130** can include the layers of P-type GaN/InGaN light-emitting layer/N-type GaN. In some embodiments, P type is generally Mg-doped, and N-type is generally Si-doped. In some examples, the thickness of the green LED light emitting layer is about 0.1 micron to about 5 microns. In a preferred embodiment, the thickness of the green LED light emitting layer is about 0.3 micron.

[0220] In some embodiments, the green LED structure includes the reflective layer **127**, the conductive layer **128**, the green LED light emitting layer **130**, the conductive layer **132**, the reflective layer **133**, the P-electrode contact pad **126**, and the N-electrode contact pad **120**.

[0221] In some embodiments, the first LED structure, e.g., the red LED structure and the second LED structure, e.g. the green LED structure, have the same central axis when the extended portions such as **164**, **166**, and portions below **128-1** of the conductive layer **128** are excluded. In some embodiments, the first LED structure and the second LED structure are aligned along the same central axis when the extended portions such as **164**, **166**, and portions below **128-1** of the conductive layer **128** are excluded.

[0222] In some embodiments, the bonding layer **160**, is used to bond the green LED structure and the blue LED structure together. In some embodiments, the bonding layer **156** is not transparent to the light emitted from the LED device **100**. In some embodiments, the materials and the thickness of the bonding layer **160** is the same as described above for the metal bonding layer **108**. In some embodiments, the bonding layer **160** can also be used as a reflector to reflect light emitted from the LED structures above.

[0223] In some embodiments, when vertical transmission is used, the bonding layer **160** is transparent to the light emitted from the LED device **100**. In some embodiments, the bonding layer **160** is made of dielectric materials such as solid inorganic materials or plastic materials same as described above for the bonding layer **156**. In some embodiments, the transparent bonding layers can facilitate the light emitted from the layers below the bonding layers to pass through.

[0224] In some embodiments, as shown in both FIGS. **1A** and **1B**, the blue LED structures has a P-electrode contact pad **152** electrically connected to the blue LED light emitting layer **136**. In some embodiments, the P-electrode contact pad **152** is connected to a conductive layer **134**. In some embodiments, the conductive layer **134** for electrode connection is formed at the bottom of the blue LED light emitting layer **136**. In some embodiments, the conductive layer **134** can be a metal layer or a conductive transparent layer, such as an ITO layer, that is formed between the blue LED light emitting layer **136** and a P-electrode contact pad **152** as shown in FIGS. **1A** and **1B** to improve conductivity and transparency.

[0225] In some embodiments, the conductive layer **134** has an extended portion **134-1** at one side of the conductive layer **134** relative to the layers above it as shown in FIG. **1B**. In some embodiments, the extended portion **134-1** is extended together with all the layers below the conductive layer **134** within the LED device **100**. In some embodiments, the blue LED light emitting layer **136** is electrically connected to the P-electrode contact pad **152** through the extended portion **134-1** of the conductive layer **134**. In some embodiments, the P-electrode contact pad **152** is also electrically connected to the driver circuit **106** in the substrate **104**.

[0226] In some embodiments, an insulation layer **174** made of dielectric materials, such as a SiO<sub>2</sub> layer, is deposited on the surface of the LED device **100**. The P-electrode contact pad **152** is extended from its contact with the driver circuit **106** to its contact with the conductive layer **134** through a via or passage within the insulation layer **174**. The P-electrode contact pad **152** does not contact with other layers within the LED device **100**.

[0227] In some embodiments, a conductive layer **138** for electrode connection is formed at the top of the blue LED light emitting layer **136**. In some embodiments, the conductive layer **138** can be a metal layer or a conductive transparent layer, such as an ITO layer, that is formed between the blue LED light emitting layer **136** and an N-electrode contact pad **140** to improve conductivity and transparency. In some embodiments, the N-electrode contract pad **140** is made of transparent conductive materials such as ITO. In some embodiments, the N-electrode contact pad **140** is made of materials such as graphene, ITO, AZO, or FTO, or any combinations thereof. In some embodiments, the N-electrode contact pads **116**, **120** and **140** are all electrically connected together as a common N-electrode. In some embodiments, the N-electrode contact pads **116**, **120** and **140** are formed as one integral piece as a common N-electrode.

[0228] In some embodiments, shown in FIG. **1B**, the blue LED structure has the N-electrode contact pad **140** electrically connected to the blue LED light emitting layer **136**. In some embodiments, the N-electrode contact pad **140** is connected to the conductive layer **138**.

[0229] In some embodiments, the lateral dimension of the blue LED light emitting layer **136** is smaller than the lateral dimension of the green LED light emitting layer **130**.

[0230] In some embodiments, the top electrode elements, such as the N-electrode pad **140**, is connected through electrical connections below the optical isolation structures, such as **146**, **148**, **170** and **172**. In some embodiments, the top electrode is connected through electrical connections embedded in the substrate **104**. In an example, the top electrode **140** is connected through electrical connection elements that is above the insulation layer **174** and below the optical isolation structures, such as **146**, **148**, **170** and **172**.

[0231] In some embodiments, a reflective layer **135** is positioned below the blue LED light emitting layer **136** between the conductive layer **134** and the bonding layer **160**. In some embodiments, an optional reflective layer **139** (not shown in FIGS. **1A-1C**) is positioned above the blue LED light emitting layer **136** on top of the conductive layer **138**.

[0232] In one approach, the blue LED light emitting layer **136** is grown on a separate substrate (referred to as the epitaxy substrate). The epitaxy substrate is then removed after bonding, for example, by a laser lift-off process or wet chemical etching, leaving the structure shown in FIGS. **1B** and **1C**.

[0233] In some embodiments, the blue LED light emitting layer **136** is for forming blue micro LEDs. Examples of a blue LED light emitting layer include III-V nitride, III-V arsenide, III-V phosphide, and III-V antimonide epitaxial structures. In some instances, films within the blue LED light emitting layer **136** can include the layers of P-type GaN/InGaN light-emitting layer/N-type GaN. In some embodiments, P type is generally Mg-doped, and N-type is generally Si-doped. In some examples, the thickness of the blue LED light emitting layer is about 0.1 micron to about 5 microns. In a preferred embodiment, the thickness of the blue LED light emitting layer is about 0.3 micron.

[0234] In some embodiments, the blue LED structure includes the reflective layer **135**, the conductive layer **134**, the blue LED light emitting layer **136**, the conductive layer **138**, the optional reflective layer **139**, the P-electrode contact pad **152**, and the N-electrode contact pad **140**.

[0235] In some embodiments, the second LED structure, e.g., the green LED structure, and the third LED structure, e.g., the blue LED structure, have the same central axis when the extended portions such as **166**, and portions below **134-1** of the conductive layer **134** are excluded. In some embodiments, the first LED structure and the second LED structure are aligned along the same central axis when the extended portions such as **166**, and portions below **134-1** of the conductive layer **134** are excluded.

[0236] In some embodiments, the N-electrode **140** covers the top of the tri-color LED device **100**. In some embodiments, the N-electrode **140** connects to an N-electrode in an adjacent tri-color LED device (not shown in FIG. **1A-1C**) via some electrical connections components, and therefore serves as a common electrode.

[0237] In some embodiments, the thickness of each of the conductive layers **110**, **114**, **128**, **132**, **134**, and **138** is about 0.01 micron to about 1 micron. In some instances, before any bonding process with the next epitaxial layer, each of the conductive layers **110**, **114**, **128**, **132**, **134**, and **138** is deposited on the respective corresponding epitaxial layer commonly by vapor deposition, for example, electron beam evaporation or sputtering deposition. In some examples, conductive layers are used to maintain a good conductivity for electrode connection while in some instances, improving optical properties of the LED devices, such as reflectivity or transparency.

[0238] In some embodiments, an additional dielectric layer (not shown in FIGS. **1A-1C**) such as a SiO<sub>2</sub> layer is formed above the bottom light emitting layer **112** (and above the conductive layer **114**), preferably above the reflective layer **115**, and below the bonding layer **156**, to electrically separate the N-type layer of the light emitting layer **112** from the bonding layer **156**. In some embodiments, the thickness of the additional dielectric layer is from 20 nanometers to 2 microns. In a preferred embodiment, the thickness of the additional dielectric layer is about 100 nanometers. In some embodiments, an additional dielectric layer (not shown in FIGS. **1A-1C**) such as a SiO<sub>2</sub> layer is formed above the middle light emitting layer **130** (and above the conductive layer **132**), preferably above the reflective layer **133**, and below the bonding layer **160**, to electrically separate the N-type layer of the light emitting layer **130** from the bonding layer **160**. In some embodiments, the thickness of the additional dielectric layer is from 20 nanometers to 2 microns. In a preferred embodiment, the thickness of the additional dielectric layer is about 100 nanometers.

[0239] In some embodiments, in order to improve the light emission efficiency from the tri-color LED device **100**, optical isolation structures as further described below such as **146**, **148**, **170** and **172** are formed along the sidewall of the tri-color LED device **100**. In some embodiments, the optical isolation structures such as **146**, **148**, **170** and **172** are made from dielectric materials such as SiO<sub>2</sub>.

[0240] As shown in FIG. **1A** from the top view, in some embodiments, the tri-color LED device

**100** has a circular shape. In some embodiments, the optical isolation structures, such as **146**, **148**, **170** and **172**, are connected as one piece and formed as a circular sidewall around the tri-color LED device **100**. In some embodiments, the optical isolation structures are formed as a reflective cup as described in further detail below. In some embodiments, the three stacked LED structures within the tri-color LED device **100** are also in circular shapes. In some embodiments, the tri-color LED device **100** can be in other shapes, such as rectangle, square, triangle, trapezoid, polygon. In some embodiments, the optical isolation structures, such as **146**, **148**, **170** and **172**, are connected as one piece and formed as a sidewall around the tri-color LED device **100** with other shapes such as rectangle, square, triangle, trapezoid, polygon.

[0241] As shown in FIGS. **1B** and **1C**, in some embodiments, the red LED light emitting layer **112**, the green LED light emitting layer **130** and the blue LED light emitting layer **136** has oblique side surfaces. As used here, the oblique side surface may refer to a surface that is not perpendicular to the top or bottom surfaces of the respective LED light emitting layer. In some embodiments, the angle between the oblique side wall and the bottom surface of the respective LED light emitting layer is less than 90 degrees. In some embodiments, the bonding layers **108**, **156** and **160** also has an oblique side surface. The oblique side surfaces may enhance easy connections for different connectors to the LED light emitting layers, prevent disconnections of those connectors because of sharp angles, and enhance the overall stability of the device.

[0242] In some embodiments, the light transmission efficiency of the multi-color LED device changes as the angle of the oblique side surface of the LED light emitting layers relative to a normal line to the surface of the substrate **104** changes. In some embodiments, the light transmission efficiency of the multi-color LED device increases as the angle of the oblique side surface of the LED light emitting layers relative to a normal line to the surface of the substrate **104** increases. For example, when the angle of the side surface of the LED light emitting layers relative to the normal line to the surface of the substrate **104** is  $\pm 5$  degrees and when the optical isolation structures such as **146**, **148**, **170** and/or **172** are not reflective cups as described below, the light emission efficiency of a multi-color LED device is 0.32%. For example, when the angle of the side surface of the LED light emitting layers relative to the normal line to the surface of the substrate **104** is  $\pm 15$  degrees and when the optical isolation structures such as **146**, **148**, **170** and/or **172** are not reflective cups as described below, the light emission efficiency of a multi-color LED device is 2.7%. For example, when the angle of the side surface of the LED light emitting layers relative to the normal line to the surface of the substrate **104** is at (for example, when the light emitting layer is tilted) or very close to  $\pm 90$  degrees and when the optical isolation structures such as **146**, **148**, **170** and/or **172** are not reflective cups as described below, the light emission efficiency of a multi-color LED device is equal to or very close to 56.4%.

[0243] In contrast, the implementation of reflective cup structures, as described in further detail below, improves the light transmission efficiency of the multi-color LED device. For example, when the angle of the side surface of the LED light emitting layers relative to the normal line to the surface of the substrate **104** is  $\pm 5$  degrees and when the optical isolation structures such as **146**, **148**, **170** and/or **172** are reflective cups as described below, the light emission efficiency of a multi-color LED device is 0.65%, that is an increase of 104.6% compared with the LED device without a reflective cup. For example, when the angle of the side surface of the LED light emitting layers relative to the normal line to the surface of the substrate **104** is  $\pm 15$  degrees and when the optical isolation structures such as **146**, **148**, **170** and/or **172** are reflective cups as described below, the light emission efficiency of a multi-color LED device is 6.65%, that is an increase of 144.4% compared with the LED device without a reflective cup. For example, when the angle of the side surface of the LED light emitting layers relative to the normal line to the surface of the substrate **104** is at (for example, when the light emitting layer is tilted) or very close to  $\pm 90$  degrees and when the optical isolation structures such as **146**, **148**, **170** and/or **172** are reflective cups as described below, the light emission efficiency of a multi-color LED device is equal to or very close

to 66.65%, that is an increase of 18.4% compared with the LED device without a reflective cup. [0244] In some embodiments, reflective layers are formed above and below each of the LED light emitting layers to improve light transmission efficiency. As shown in both FIGS. 1B and 1C, in some embodiments, a reflective layer **109** is formed between the bonding layer **108** and the red LED light emitting layer **112**. In some embodiments, the reflective layer **109** is formed between the bonding layer **108** and the conductive layer **110** when the conductive layer **110** is present. In some embodiments, a reflective layer **115** is formed between the bonding layer **156** and the red LED light emitting layer **112**. In some embodiments, the reflective layer **115** is formed between the bonding layer **156** and the conductive layer **114** when the conductive layer **114** is present.

[0245] In some embodiments, a reflective layer **127** is formed between the bonding layer **156** and the green LED light emitting layer **130**. In some embodiments, the reflective layer **127** is formed between the bonding layer **156** and the conductive layer **128** when the conductive layer **128** is present. In some embodiments, a reflective layer **133** is formed between the bonding layer **160** and the green LED light emitting layer **130**. In some embodiments, the reflective layer **133** is formed between the bonding layer **160** and the conductive layer **132** when the conductive layer **132** is present.

[0246] In some embodiments, a reflective layer **135** is formed between the bonding layer **160** and the blue LED light emitting layer **136**. In some embodiments, the reflective layer **135** is formed between the bonding layer **160** and the conductive layer **134** when the conductive layer **134** is present. In some embodiments, an optional reflective layer **139** (not shown in FIGS. 1B-1C) is formed between the N-electrode pad **140** and the blue LED light emitting layer **136**, while still allowing the blue LED light emitting layer **136** to be electrically connected to the N-electrode pad **140**, for example, through a conductive path. In some embodiments, the optional reflective layer **139** is formed between the N-electrode pad **140** and the conductive layer **138** when the conductive layer **138** is present, while still allowing the conductive layer **138** to be electrically connected to the N-electrode pad **140**, for example, through a conductive path.

[0247] In some embodiments, the materials of the reflective layers **109**, **115**, **127**, **133**, **135** and **139** have a high reflectivity, especially to the light emitted by the single pixel tri-color LED device **200**. For example, the reflectivity of the reflective layers **109**, **115**, **127**, **133**, **135** and **139** is above 60%. In another example, the reflectivity of the reflective layers **109**, **115**, **127**, **133**, **135** and **139** is above 70%. In yet another example, the reflectivity of the reflective layers **109**, **115**, **127**, **133**, **135** and **139** is above 80%.

[0248] In some embodiments, the material of the reflective layers **109**, **115**, **127**, **133**, **135** and **139** is metal selected from one or more of Rh, Al, Ag, and Au. In some embodiments, any one of the reflective layers **109**, **115**, **127**, **133**, **135** and **139** can include at least two sublayers with different refractive index. Each of the sublayers also has a high reflectivity such as above 60%, 70% or 80%.

[0249] In some embodiments, each of the reflective layers, such as **109**, **115**, **127**, **133**, **135** and **139**, is coated on both sides of each of the light emitting layers such as **112**, **130** and **136**, or the conductive layers **110**, **114**, **128**, **132**, **134**, and **138**, when the conductive layers are included before bonding. In some instances, the thickness of each of the reflective layers such as **109**, **115**, **127**, **133**, **135** and **139**, is about 2 nanometers (nm) to about 5 microns. In some embodiments, the thickness of each of the reflective layers such as **109**, **115**, **127**, **133**, **135** and **139**, is equal to or below 1 micron. In some preferred embodiments, the thickness of each of the reflective layers such as **109**, **115**, **127**, **133**, **135** and **139**, is about 5 nanometers (nm) to 10 nm.

[0250] In some embodiments, any one of the reflective layers, such as **109**, **115**, **127**, **133**, **135** and **139**, includes a distributed Bragg reflector (DBR) structure. For example, any one of the reflective layers, such as **109**, **115**, **127**, **133**, **135** and **139**, is formed from multiple layers of alternating or different materials with varying refractive index. In some instances, each layer boundary of the DBR structure causes a partial reflection of an optical wave. The reflective layers, such as **109**, **115**, **127**, **133**, **135** and **139**, can be used to reflect some selected wavelengths, for example, reflective

layers **109** and **115** for red light, reflective layers **127** and **133** for green light, and reflective layers **135** and **139** for blue light. In some embodiments, any one of the reflective layers, such as **109**, **115**, **127**, **133**, **135** and **139**, is made of multiple layers, e.g., at least two layers, of SiO<sub>2</sub> and Ti<sub>3</sub>O<sub>5</sub>, respectively. By varying the thicknesses and numbers of layers of SiO<sub>2</sub> and Ti<sub>3</sub>O<sub>5</sub> respectively, selective reflection or transmission of light at different wavelengths can be formed.

[0251] In some embodiments, any one of the reflective layers, such as **109**, **115**, **127**, **133**, **135** and **139**, further includes a transparent layer on one of the high reflectivity sub-layers. For example, the transparent layer, preferably formed on either side of the reflective layer, such as **109**, **115**, **127**, **133**, **135** and **139**, is selected from one or more of ITO and SiO<sub>2</sub>.

[0252] In some embodiments, each of the reflective layers **109** and **115** for a red light LED include multiple layers of Au or/and Indium Tin Oxide (ITO).

[0253] In some embodiments, each of the reflective layers **109** and **115** for a red light LED structure has a low absorbance (for example, equal to or less than 25%) of the light generated by different layers of the tri-color LED device **100**. In some embodiments, each of the reflective layers **109** and **115** for a red light LED structure has a high reflectance (for example, equal to or more than 75%) of the light generated between the current two reflective layers **109** and **115**, for example, the red light.

[0254] In one example, the following DBR structure shown in table 1 is used to reflect green light from a green light LED:

TABLE-US-00001 TABLE 1 DBR layer structure for a green light LED reflective layer. Layer  
Layer thickness composition (in nanometer) SiO<sub>2</sub> 1000 TiO<sub>2</sub> 109.54 SiO<sub>2</sub> 318.48 TiO<sub>2</sub> 64.95  
SiO<sub>2</sub> 106.07 TiO<sub>2</sub> 245.76 SiO<sub>2</sub> 137.08 TiO<sub>2</sub> 65.14 SiO<sub>2</sub> 106.77 TiO<sub>2</sub> 338.95 SiO<sub>2</sub> 37.27 TiO<sub>2</sub>  
12.41 SiO<sub>2</sub> 352.18 TiO<sub>2</sub> 70.83 SiO<sub>2</sub> 229.25 ITO 20

[0255] In some embodiments, each of the reflective layers **127** and **133** for a green light LED structure has a low absorbance (for example, equal to or less than 25%) of the light generated by different layers of the tri-color LED device **100**. In some embodiments, each of the reflective layers **127** and **133** for a green light LED structure has a high reflectance (for example, equal to or more than 75%) of the light generated between the current two reflective layers **127** and **133**, for example, the green light.

[0256] In one example, the following DBR structure shown in table 2 is used to reflect blue light from a blue light LED:

TABLE-US-00002 TABLE 2 DBR layer structure for a blue light LED reflective layer. Layer  
Layer thickness composition (in nanometer) SiO<sub>2</sub> 1000 SiO<sub>2</sub> 183.36 TiO<sub>2</sub> 96 SiO<sub>2</sub> 84.65 TiO<sub>2</sub>  
51.37 SiO<sub>2</sub> 332.37 TiO<sub>2</sub> 79.95 SiO<sub>2</sub> 423.13 TiO<sub>2</sub> 52.99 SiO<sub>2</sub> 35.87 TiO<sub>2</sub> 235.03 SiO<sub>2</sub> 253.67  
TiO<sub>2</sub> 64.38 SiO<sub>2</sub> 336.08 ITO 20

[0257] In some embodiments, each of the reflective layers **135** and optionally **139** for a blue light LED structure has a low absorbance (for example, equal to or less than 25%) of the light generated by different layers of the tri-color LED device **100**. In some embodiments, the reflective layer **135** for a blue light LED structure has a high reflectance (for example, equal to or more than 75%) of the light generated above the current reflective layer **135** or between the current reflective layers **135** and **139**, for example, the blue light.

[0258] FIG. 2A is a cross-sectional view of a single pixel tri-color LED device **100** along the diagonal line **102** in FIG. 1A with planarization, in accordance with some embodiments. In some embodiments, the single pixel tri-color LED device **100** has similar structures as the single pixel tri-color LED device **100** shown in FIGS. 1A, 1B and 1C with the addition of a planarized layer **176** covering the single pixel tri-color LED device **100**.

[0259] FIG. 2B is a cross-sectional view of a single pixel tri-color LED device **100** along the diagonal line **150** in FIG. 1A with planarization, in accordance with some embodiments. In some embodiments, the single pixel tri-color LED device **100** has similar structures as the single pixel tri-color LED device **100** shown in FIGS. 1A, 1B and 1C with the addition of a planarized layer

**176** covering the single pixel tri-color LED device **100**.

[0260] In some embodiments, the planarized layer, such as **176**, is transparent to the light emitted from the micro LED **100**. In some embodiments, the planarized layer is made of dielectric materials such as solid inorganic materials or plastic materials. In some embodiments, the solid inorganic materials include SiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, Si<sub>3</sub>N<sub>4</sub>, Phosphosilicate glass (PSG), or Borophosphosilicate glass (BPSG), or any combination thereof. In some embodiments, the plastic materials include polymers such as SU-8, PermiNex, Benzocyclobutene (BCB), or transparent plastic (resin) including spin-on glass (SOG), or bonding adhesive Micro Resist BCL-1200, or any combination thereof. In some embodiments, the planarized layer can facilitate the light emitted from the micro LED **100** to pass through.

[0261] In some embodiments, the planarized layer **176** has the same height as the optical isolation structures, for example **146**, **148**, **170** and **172**, relative to the surface of the substrate **104**. For example, the planarized layer **176** covers the whole single pixel tri-color LED device **100** and the sidewall of the optical isolation structures. The planarized layer **176** is on the same plane as the top surface of the optical isolation structures.

[0262] FIG. 3A is a cross-sectional view of a single pixel tri-color LED device **100** along the diagonal line **102** in FIG. 1A with planarization, in accordance with some embodiments. In some embodiments, the single pixel tri-color LED device **100** has similar structures as the single pixel tri-color LED device **100** shown in FIGS. 1A, 1B and 1C with the addition of a planarized layer **178** covering the single pixel tri-color LED device **100**.

[0263] FIG. 3B is a cross-sectional view of a single pixel tri-color LED device **100** along the diagonal line **150** in FIG. 1A with planarization, in accordance with some embodiments. In some embodiments, the single pixel tri-color LED device **100** has similar structures as the single pixel tri-color LED device **100** shown in FIGS. 1A, 1B and 1C with the addition of a planarized layer **178** covering the single pixel tri-color LED device **100**.

[0264] In some embodiments, the planarized layer **178** has the same height as the top electrode elements, for example **140**. The planarized layer **178** is on the same plane as the top surface of the top electrode elements, such as the N-electrode pad **140**. In some embodiments, the top electrode elements, for example **140**, is right on top of the planarized layer **178**. The planarized layer **178** is on the same plane as the bottom surface of the top electrode elements, such as the N-electrode pad **140**. For example, the planarized layer **178** covers the whole single pixel tri-color LED device **100** and a portion of the sidewall of the optical isolation structures, for example **146**, **148**, **170** and **172**.

[0265] Unlike the electrode connections shown in FIG. 1A-1C, where the top electrode elements, such as the N-electrode pad **140**, is connected through electrical connections below the optical isolation structures, such as **146**, **148**, **170** and **172**, in FIGS. 2A-2B, 3A-3B, the top electrode elements, such as the N-electrode pad **140**, is connected through electrical connections at least at the sidewall of the optical isolation structures such as **146**, **148**, **170** and **172**. In some embodiments, the N-electrode pad **140** is fixed through or on a surface of the optical isolation structures, such as **146**, **148**, **170** and **172**. The top electrode structure can simplify the fabrication process especially with the planarized layer and the make the single pixel tri-color LED device **100** compact.

[0266] In some embodiments, an insulation layer can be deposited on the single pixel multi-color LED device on the LED light emitting layers and other layers such as the conductive layers and reflective layers. A planarization process is then followed to even the surface of the insulation layer that embeds the single pixel multi-color LED device. Vias for electrical connections are also formed within the planarized layers. Compared with some other processes without planarized insulation layers, the features and layers within the planarized LED structures are better protected and less susceptible to the outside destruction force. Furthermore, the planarized surface can improve the light transmission efficiency by reducing deflection from an uneven surface.

[0267] In some embodiments, through dry etching and wet etching, a tri-color LED structure is

formed and the axes of LED structures of different colors are aligned with one another vertically. In some embodiments, the LED structures of different colors share the same axis.

[0268] In some embodiments, each of the LED structures of different colors form a pyramid like shape or a trapezoidal cross-sectional shape. Each layer has a narrower width or smaller area compared to a layer beneath it. In this instance, the width or area is measured by the dimensions of a plane parallel to the surface of the substrate **104**.

[0269] In some embodiments, each of the LED structures of different colors are bonded together by bonding layers that only cover the area of the LED structures without extension beyond the area of the LED structures, the whole multi-color LED device, forms a pyramid (or inverted cone) like shape or a trapezoidal cross-sectional shape (as shown in FIGS. **1-3**). In some embodiments, the lateral dimension of the bottom LED structure, for example, the red LED structure, can be the longest, and the lateral dimension of the top LED structure, for example, the blue LED structure, can be the shortest. A pyramid like shape can be formed naturally when each of the layers within the LED device is etched and patterned from bottom up. A pyramid like structure can improve the electronic connections between the individual LED structures and to the electrodes, and simplify the fabrication process. For example, the electrode connections are exposed in each layer for easy connection.

[0270] In some embodiments, the bottom layer such as the metal bonding layer **108** has a lateral dimension of about 1 micron to about 500 microns. In a preferred embodiment, the lateral dimension of the metal bonding layer **108** at the bottom of the multi-color LED device is about 1.75 microns. In some embodiments, the vertical height of the multi-color LED device is about 1 micron to about 500 microns. In a preferred embodiment, the vertical height of the multi-color LED device is about 1.9 microns. In a preferred embodiment, the lateral dimension of the conductive layer **138** at the top of the multi-color LED device is about 1.0 micron.

[0271] In some embodiments, the aspect ratio of a cross section of a layer of the tri-color LED device remains substantially the same when the lateral dimension of the same layer varies. For example, when the lateral dimension of a patterned epitaxial layer is 5 microns, the thickness of the patterned epitaxial layer is less than a micron. In another example, when the lateral dimension of the same patterned epitaxial layer increases, the thickness of the same patterned epitaxial layer increases accordingly to maintain the same aspect ratio. In some embodiments, the aspect ratio of the cross-section of the epitaxial layers and other layers is less than 1/5 in thickness/width.

[0272] The shape of the LED device is not limited and in some other embodiments, the cross-sectional shape of the tri-color LED device can take the form of other shapes, for example, a reverse trapezoid, a semi-oval, a rectangle, a parallelogram, a triangle, or a hexagon, etc.

[0273] In some embodiments, the top conductive layer **138** above the third LED light emitting layer **136** is patterned using photolithography and etching. In some instances, the etching method used to form the pattern is dry etching, for example, inductively coupled plasma (ICP) etching, or wet etching with an ITO etching solution. In some embodiments, the same patterning methods can apply to all the other conductive layers, including conductive layers **110**, **114**, **128**, **132**, **134**, and **138** within the tri-color LED device **100**.

[0274] In some embodiments, the blue LED light emitting layer **136** and the green LED light emitting layer **130** are patterned using photolithography and etching. In some instances, the etching method used to form the pattern is dry etching, for example, inductively coupled plasma (ICP) etching, with Cl<sub>2</sub> and BCl<sub>3</sub> etching gases.

[0275] In some embodiments, the bonding layers including **160** and **156** are patterned using photolithography and etching. In some instances, the etching method used to form the pattern is dry etching, for example, inductively coupled plasma (ICP) etching, with CF<sub>4</sub> and O<sub>2</sub> etching gases.

[0276] In some embodiments, the reflective layers including **109**, **115**, **127**, **133**, **135** and **139** are patterned using photolithography and etching. In some instances, the etching method used to form the pattern for the reflective layers especially the DBR layers is dry etching, for example,



inductively coupled plasma (ICP) etching, with CF<sub>4</sub> and O<sub>2</sub> etching gases, or ion beam etching (IBE) with Ar gas.

[0277] In some embodiments, the red LED light emitting layer **112** is patterned using photolithography and etching. In some instances, the etching method used to form the pattern is dry etching, for example, inductively coupled plasma (ICP) etching, with Cl<sub>2</sub> and HBr etching gases.

[0278] In some embodiments, the metal bonding layer **108** is patterned using photolithography and etching. In some instances, the etching method used to form the pattern is dry etching, for example, inductively coupled plasma (ICP) etching, with Cl<sub>2</sub>/BCl<sub>3</sub>/Ar etching gases, or ion beam etching (IBE) with Ar gas.

[0279] In some embodiments, after each of the LED device structures is patterned, an insulation layer, such as **174**, **176**, **178**, is deposited on the surface of the patterned LED structure including all the patterned layers, side walls, and the exposed substrate. In some embodiments, the insulation layer is made of SiO<sub>2</sub> and/or Si<sub>3</sub>N<sub>4</sub>. In some embodiments, the insulation layer is made of TiO<sub>2</sub>. In some embodiments, the insulation layer is formed with composition similar to SiO<sub>2</sub> after curing a layer such as SOG at a high temperature. In some embodiments, the insulation layer is made of a material that has a similar thermal coefficient of the layers underneath the insulation layer. The surface of the insulation layers, such as **176** and **178**, is then smoothed or planarized by a relevant method understood by a person of ordinary skill in the art, such as chemical mechanical polishing.

[0280] In some embodiments, the insulation layers, such as **176** and **178** after planarization are patterned to expose the electrode contact area using photolithography and etching. In some instances, the etching method used to form the pattern is dry etching, for example, inductively coupled plasma (ICP) etching, with CF<sub>4</sub> and O<sub>2</sub>.

[0281] In some embodiments, P-electrode or anode metal pads are vapor deposited, or by other deposition method, on a suitable location of the patterned LED structure, such as on one side and/or in vias within the planarized insulation layer, to electrically connect the red LED structure, the green LED structure, and the blue LED structure.

[0282] In some embodiments, separate N-electrode or cathode metal pads are vapor deposited, or by other deposition method, on a suitable location of the patterned LED structure, such as on one side/top and/or in vias within the planarized insulation layer, to electrically connect the red LED structure, the green LED structure, and the blue LED structure.

[0283] FIG. **4A** is a top view of a single pixel tri-color LED device **400** with layered planarization, in accordance with some embodiments.

[0284] FIG. **4B** is a cross-sectional view of a single pixel tri-color LED device **400** along the diagonal line **402** in FIG. **4A** with layered planarization, in accordance with some embodiments. The diagonal line passes through the center of the single pixel tri-color LED device **400**.

[0285] Compared with the embodiments depicted in FIGS. **1-3**, the main difference in the embodiments in FIG. **4A-4B** is that each of the LED structures of different colors is embedded in a respective planarized insulation layer and the planarized insulation layers with the LED structure inside are then bonded together via some bonding layers.

[0286] In some embodiments, the tri-color LED device **400** includes a substrate **404**. For convenience, “up” is used to mean away from the substrate **404**, “down” means toward the substrate **404**, and other directional terms such as top, bottom, above, below, under, beneath, etc. are interpreted accordingly. The supporting substrate **404** is the substrate on which the array of individual driver circuits **406** is fabricated. In some embodiments, the driver circuits could also be located in one of the layers above the substrate **404**, or above the micro tri-color LED structure **400**. Each driver circuit is a pixel driver **406**. In some instances, the driver circuits **406** are thin-film transistor pixel drivers or silicon CMOS pixel drivers. In one embodiment, the substrate **404** is a Si substrate. In another embodiment, the supporting substrate **404** is a transparent substrate, for example, a glass substrate. Other example substrates include GaAs, GaP, InP, SiC, ZnO, and sapphire substrates. In some embodiments, the substrate **404** is around 700 microns thick. The

driver circuits **406** form individual pixel drivers to control the operation of the individual single pixel tri-color LED device **400**. The circuitry on substrate **404** includes contacts to each individual driver circuit **406** and also a ground contact. As shown in both FIG. **4A** and FIG. **4B**, each micro tri-color LED structure **400** also has two types of contacts: P-electrodes or anodes, such as **450** (or **408**), **452**, and the combined section **422**, **424** and **426**, which are connected to the pixel driver; and N-electrodes or cathodes, such as **440**, **442**, **444**, and the combined section **416**, **418**, and **420**, which are connected to the ground (i.e., the common electrode).

[0287] In some embodiments, the N-electrode (or N-electrodes contact pad) and its connections, such as **440**, **442**, **444**, and the combined section **416**, **418**, and **420**, are made of materials such as graphene, ITO, Aluminum-Doped Zinc Oxide (AZO), or Fluorine doped Tin Oxide (FTO), or any combinations thereof. In some embodiments, the N-electrode (or N-electrodes contact pad) and its connections, such as **440**, **442**, **444**, and the combined section **416**, **418**, and **420**, are made of non-transparent or transparent conductive materials and in a preferred embodiment, transparent conductive materials. In some embodiments, the P-electrode (or P-electrodes contact pad) and its connections, such as **450**, **452**, and the combined section **422**, **424** and **426**, are made of materials such as graphene, ITO, AZO, or FTO, or any combinations thereof. In some embodiments, the P-electrode (or P-electrodes contact pad) and its connections, such as **450**, **452**, and the combined section **422**, **424** and **426**, are made of non-transparent or transparent conductive materials and in a preferred embodiment, transparent conductive materials. In some embodiments, the locations of the P-electrodes (or P-electrodes contact pad) and its connections, and N-electrodes (or N-electrodes contact pad) and its connections can be switched.

[0288] In general, an LED light emitting layer includes a PN junction with a p-type region/layer and an n-type region/layer, and an active layer between the p-type region/layer and n-type region/layer.

[0289] In some embodiments, the light emitted from the red LED light emitting layer **412** is able to horizontally propagate toward the sidewall of the red LED light emitting layer **412**, then is reflected upward by a reflective element, such as **446** and/or **448**, as described below and emitted out at the top surface of the single pixel tri-color LED device **400**. As described below, a reflective layer **409** is positioned below the red LED light emitting layer **412** and a reflective layer **415** is positioned above the red LED light emitting layer **412**. The light emitted from the red LED light emitting layer **412** is reflected between the two reflective layers **409** and **415** toward the sidewall of the red LED light emitting layer **412**.

[0290] In some embodiments, the light emitted from the green LED light emitting layer **430** is able to horizontally propagate toward the sidewall of the green LED light emitting layer **430**, then is reflected upward by a reflective element, such as **446** and/or **448**, as described below and emitted out at the top surface of the single pixel tri-color LED device **400**. As described below, a reflective layer **427** is positioned below the green LED light emitting layer **430** and a reflective layer **433** is positioned above the green LED light emitting layer **430**. The light emitted from the green LED light emitting layer **430** is reflected between the two reflective layers **427** and **433** toward the sidewall of the green LED light emitting layer **430**.

[0291] In some embodiments, the light emitted from the blue LED light emitting layer **436** is able to horizontally propagate toward the sidewall of the blue LED light emitting layer **436**, then is reflected upward by a reflective element, such as **446** and/or **448**, as described below and emitted out at the top surface of the single pixel tri-color LED device **400**. As described below, a reflective layer **435** is positioned below the blue LED light emitting layer **436**. The light emitted from the blue LED light emitting layer **436** is reflected between the reflective layer **435** and the upper surface of the blue LED light emitting layer **436** toward the sidewall of the blue LED light emitting layer **436**.

[0292] In some embodiments, the light emitted from the red LED light emitting layer **412** is able to propagate vertically through the green LED light emitting layer **430** and then through the blue LED

light emitting layer **436** to be emitted out of the tri-color LED device **400**. In some embodiments, the light emitted from the green LED light emitting layer **430** is able to propagate through the blue LED light emitting layer **436** to be emitted out of the tri-color LED device **400**. In the case of vertical light transmission, in some embodiments, the top reflective layers above each of the light emitting layers, such as **415** and **433**, are preferably not included in the tri-color LED device **400**. [0293] In some embodiments, an LED light emitting layer such as **412**, **430**, and **436** includes many epitaxial sub-layers with different compositions. Examples of the LED epitaxial layers include III-V nitride, III-V arsenide, III-V phosphide, and III-V antimonide epitaxial structures. Examples of micro LEDs include GaN based UV/blue/green micro LEDs, AlInGaP based red/orange micro LEDs, and GaAs or InP based infrared (IR) micro LEDs.

[0294] In some embodiments, each of the stacked LED structures can be controlled individually to generate its individual light. In some embodiments, the combined light from the top LED epitaxial layer as a result from the operations all the LED epitaxial layers in the tri-color LED device **400** can change the color of the single pixel on a display panel within a small footprint.

[0295] In some embodiments, depending on the design of the LED device **400**, the emitted colors of the LED structures included in the same device are not limited to red, green and blue. For example, suitable colors can be selected from a range of different colors from a wavelength of 380 nm to 700 nm in visible color range. In some embodiments, LED structures emitting other colors from invisible range such as ultra-violet and infrared can be implemented.

[0296] In some embodiments, when vertical light emission is combined with horizontal light emission, for example, the three-color choice, from bottom to top can be red, green, and blue. In another embodiment, the three-color choice, from bottom to top can be infrared, orange, and ultra-violet. In some embodiments, the wavelength of the light from the LED structure on one layer of the device **400** is longer than the wavelength from the LED structure on a layer on top of the current layer. For instance, the wavelength of the light from the bottom LED light emitting layer **412** is longer than that of the middle LED light emitting layer **430**, and the wavelength of the light from the middle LED light emitting layer **430** is longer than that of the top LED light emitting layer **436**.

[0297] In some embodiments, when in a horizontal light emission case or when the portion of horizontal light emission is more than the portion of vertical light emission from the top surface of the LED device **400**, each of the LED light emitting layers **412**, **430** and **436** can be any suitable visible or invisible color. The advantage of the horizontal light emission is that since the light emitted does not need to go through the other top layers of the LED device **400** but from the edge or sidewall of the current light emitting layer directly, less light transmission loss and higher light emission efficiency can be achieved. For example, compared with the vertical light emission LED device, the horizontal light emission LED device may get 15% more, 50% more, 100% more, 150% more, or 200% more light transmission efficiency. In some instances, the light transmission efficiency from a horizontal light emission LED device can be equal to or greater than 20%, 40% or 60%.

[0298] In some embodiments, the bottom red LED light emitting layer **412** is bonded to the substrate **404** through a metal bonding layer **408**. The metal bonding layer **408** may be disposed on the substrate **404**. In one approach, a metal bonding layer **408** is grown on the substrate **404**. In some embodiments, the metal bonding layer **408** is electrically connected to both the driver circuit **406** on the substrate **404** and the red LED light emitting layer **412** above the metal bonding layer **408**, acting like a P-electrode. In some embodiments, the thickness of the metal bonding layer **408** is about 0.1 micron to about 3 microns. In a preferred embodiment, the thickness of a metal bonding layer **408** is about 0.3  $\mu\text{m}$ . The metal bonding layer **408** may include ohmic contact layers, and metal bonding layers. In some instances, two metal layers are included in the metal bonding layer **408**. One of the metal layers is deposited the layer above the metal bonding layer within the LED device **400**. A counterpart bonding metal layer is also deposited on the substrate **404**. In some

embodiments, compositions for the metal bonding layer **408** include Au—Au bonding, Au—Sn bonding, Au—In bonding, Ti—Ti bonding, Cu—Cu bonding, or a mixture thereof. For example, if Au—Au bonding is selected, the two layers of Au respectively need a Cr coating as an adhesive layer, and Pt coating as an anti-diffusion layer. And the Pt coating is between the Au layer and the Cr layer. The Cr and Pt layers are positioned on the top and bottom of the two bonded Au layers. In some embodiments, when the thicknesses of the two Au layers are about the same, under a high pressure and a high temperature, the mutual diffusion of Au on both layers bond the two layers together. Eutectic bonding, thermal compression bonding, and transient liquid phase (TLP) bonding are example techniques that may be used.

[0299] In some embodiments, the metal bonding layer **408** can also be used as a reflector to reflect light emitted from the LED structures above.

[0300] In some embodiments, a conductive layer **410** for electrode connection is formed at the bottom of the red LED light emitting layer **412**. In some embodiments, the conductive layer **410** is a conductive transparent layer **410** transparent to the light emitted from the LED device **400**, such as an Indium tin oxide (ITO) layer, that is formed between the red LED light emitting layer **412** and the metal bonding layer **408** to improve conductivity and transparency. In some embodiments, as shown in FIG. **4A** and not shown in FIG. **4B**, the red LED structure has a P-electrode contact pad **450** electrically connected to the red LED light emitting layer **412**. In some embodiments, the P-electrode contact pad **450** is connected to the conductive layer **410**. In some embodiments, a conductive layer **414** for electrode connection is formed at the top of the red LED light emitting layer **412**. In some embodiments, the conductive layer **414** is a conductive transparent layer **414**, such as an ITO layer, that is formed between the red LED light emitting layer **412** and an N-electrode contact pad **416** to improve conductivity and transparency.

[0301] In some embodiments, the red LED light emitting layer **412** has an extended portion **464** relative to the layers above it at one side of the red LED light emitting layer **412**. In some embodiments, the extended portion **464** is extended with the conductive layers **410** and **414**. In some embodiments, the extended portion **464** is connected to the N-electrode contact pad **416** through the extended portion of the conductive layer **414** above the extended portion **464**.

[0302] In some embodiments, a reflective layer **409** is positioned below the red LED light emitting layer **412** between the conductive layer **410** and the metal bonding layer **408**, and a reflective layer **415** is positioned above the red LED light emitting layer **412** between the conductive layer **414** and a bonding layer **456**, and in one example, within a planarized insulation layer **454**.

[0303] In one approach, the red LED light emitting layer **412** is grown on a separate substrate (referred to as the epitaxy substrate). The epitaxy substrate is then removed after bonding, for example, by a laser lift-off process or wet chemical etching, leaving the structure shown in FIG. **4B**.

[0304] In some embodiments, the red LED light emitting layer **412** is for forming red micro LEDs. Examples of a red LED light emitting layer include III-V nitride, III-V arsenide, III-V phosphide, and III-V antimonide epitaxial structures. In some instances, films within the red LED light emitting layer **412** can include the layers of P-type GaP/P-type AlGaInP light-emitting layer/AlGaInP/N-type AlGaInP/N-type GaAs. In some embodiments, P type layer is generally Mg-doped, and N-type layer is generally Si-doped. In some examples, the thickness of the red LED light emitting layer is about 0.1 micron to about 5 microns. In a preferred embodiment, the thickness of the red LED light emitting layer is about 0.3 micron.

[0305] In some embodiments, the red LED structure includes the metal bonding layer **408**, the reflective layer **409**, the conductive layer **410**, the red LED light emitting layer **412**, the conductive layer **414**, the reflective layer **415**, and the N-electrode contact pad **416**. In some embodiments, the red LED structure is formed within a planarized insulation layer **454**, for example, Silicon Dioxide (SiO<sub>2</sub>) layer. In some embodiments, the planarized insulation layer **454** covers the whole red LED structure. In some embodiments, the whole red LED structure is embedded within the planarized

insulation layer **454**. In some embodiments, the surface of the planarized insulation layer **454** is smoothed or planarized by the method of chemical mechanical polishing.

[0306] In some embodiments, the planarized layer, such as **454**, is transparent to the light emitted from the micro LED **400**. In some embodiments, the planarized layer is made of dielectric materials such as solid inorganic materials or plastic materials. In some embodiments, the solid inorganic materials include SiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, Si<sub>3</sub>N<sub>4</sub>, Phosphosilicate glass (PSG), or Borophosphosilicate glass (BPSG), or any combination thereof. In some embodiments, the plastic materials include polymers such as SU-8, PermiNex, Benzocyclobutene (BCB), or transparent plastic (resin) including spin-on glass (SOG), or bonding adhesive Micro Resist BCL-1200, or any combination thereof. In some embodiments, the planarized layer can facilitate the light emitted from the micro LED **400** to pass through. In some embodiments, the planarized layers such as **454**, **468**, and **462** have the same composition as the bonding layer such as **456** and **460**. In some embodiments, the planarized layers such as **454**, **468**, and **462** have different composition than the bonding layer such as **456** and **460**.

[0307] In some embodiments, a via or through hole is formed within the planarized insulation layer **454** to accommodate the P-electrode contact components **422** and **424** for the green LED structure. The P-electrode contact components **422** and **424** are connected to a driver circuit **406**.

[0308] In some embodiments, the bonding layer **456**, is used to bond the red LED structure and the green LED structure together. In some embodiments, the bonding layer **456** is not transparent to the light emitted from the LED device **400**. In some embodiments, the materials and the thickness of the bonding layer **456** is the same as described above for the metal bonding layer **408**. In some embodiments, the bonding layer **456** can also be used as a reflector to reflect light emitted from the LED structures above.

[0309] In some embodiments, when vertical transmission is used, the bonding layer **456** is transparent to the light emitted from the micro LED **400**. In some embodiments, the bonding layer **456** is made of dielectric materials such as solid inorganic materials or plastic materials. In some embodiments, the solid inorganic materials include SiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, Si<sub>3</sub>N<sub>4</sub>, Phosphosilicate glass (PSG), or Borophosphosilicate glass (BPSG), or any combination thereof. In some embodiments, the plastic materials include polymers such as SU-8, PermiNex, Benzocyclobutene (BCB), or transparent plastic (resin) including spin-on glass (SOG), or bonding adhesive Micro Resist BCL-1200, or any combination thereof. In some embodiments, the transparent bonding layers can facilitate the light emitted from the layers below the bonding layers to pass through.

[0310] In some embodiments, a conductive layer **428** for electrode connection is formed at the bottom of the green LED light emitting layer **430**. In some embodiments, the conductive layer **428** is a conductive transparent layer **428**, such as an ITO layer, that is formed between the green LED light emitting layer **430** and the bonding layer **456** to improve conductivity and transparency.

[0311] In some embodiments, as shown in both FIG. 4A and in FIG. 4B, the green LED structures has a P-electrode contact pad **426** electrically connected to the green LED light emitting layer **430**. In some embodiments, the P-electrode contact pad **426** is connected to the conductive layer **428**. In some embodiments, the P-electrode contact pad **426** is also connected to the P-electrode contact components **422** and **424** within the planarized insulation layer **454** through a portion of the P-electrode contact pad **426** within the bonding layer **456**. In some embodiments, the P-electrode contact component **422** has a cylindrical shape. In some embodiments, the P-electrode contact component **424** has a funnel like shape with the top side narrow that matches the width of the component **422** and the bottom side wide, and this shape is to support the component **422** above it. In some embodiments, a conductive layer **432** for electrode connection is formed at the top of the green LED light emitting layer **430**. In some embodiments, the conductive layer **432** is a conductive transparent layer **432**, such as an ITO layer, that is formed between the green LED light emitting layer **430** and an N-electrode contact pad **420** to improve conductivity and transparency. In some embodiments, shown in both FIG. 4A and in FIG. 4B, the green LED structure has the N-

electrode contact pad **420** electrically connected to the green LED light emitting layer **430**. In some embodiments, the N-electrode contact pad **420** is connected to the conductive layer **432**. In some embodiments, the N-electrode contact pad **420** of the green LED structure is also electrically connected to the N-electrode contact pad **416** of the red LED structure through an N-electrode contact component **418** within the transparent bonding layer **456**. In some embodiments, vias or through holes are formed within the bonding layer **456** to accommodate a portion of the P-electrode contact pad **426** and the N-electrode contact component **418**.

[0312] In some embodiments, the green LED light emitting layer **430** has an extended portion **466** relative to the layers above it at one side of the green LED light emitting layer **430**. In some embodiments, the extended portion **466** is extended with the conductive layers **428** and **432**. In some embodiments, the extended portion **466** is connected to the N-electrode contact pad **420** through the extended portion of the conductive layer **432** above the extended portion **466**.

[0313] In some embodiments, the lateral dimension of the green LED light emitting layer **430** is substantially the same as the lateral dimension of the red LED light emitting layer **412**, especially for the effective light emitting area.

[0314] In some embodiments, a reflective layer **427** is positioned below the green LED light emitting layer **430** between the conductive layer **428** and the bonding layer **456**, and a reflective layer **433** is positioned above the green LED light emitting layer **430** between the conductive layer **432** and a bonding layer **460**, in one example, within a planarized insulation layer **458**.

[0315] In one approach, the green LED light emitting layer **430** is grown on a separate substrate (referred to as the epitaxy substrate). The epitaxy substrate is then removed after bonding, for example, by a laser lift-off process or wet chemical etching, leaving the structure shown in FIG. **4B**.

[0316] In some embodiments, the green LED light emitting layer **430** is for forming green micro LEDs. Examples of a green LED light emitting layer include III-V nitride, III-V arsenide, III-V phosphide, and III-V antimonide epitaxial structures. In some instances, films within the green LED light emitting layer **430** can include the layers of P-type GaN/InGaN light-emitting layer/N-type GaN. In some embodiments, P type is generally Mg-doped, and N-type is generally Si-doped. In some examples, the thickness of the green LED light emitting layer is about 0.1 micron to about 5 microns. In a preferred embodiment, the thickness of the green LED light emitting layer is about 0.3 micron.

[0317] In some embodiments, the green LED structure includes the reflective layer **427**, the conductive layer **428**, the green LED light emitting layer **430**, the conductive layer **432**, the reflective layer **433**, and the N-electrode contact pad **420**. In some embodiments, the green LED structure is formed within a planarized insulation layer **458**. In some embodiments, the planarized insulation layer **458** covers the whole green LED structure and a portion of the P-electrode contact pad **426**. In some embodiments, the whole green LED structure is embedded within the planarized insulation layer **458**. In some embodiments, both surfaces of the planarized insulation layer **458** is smoothed or planarized by the method of chemical mechanical polishing.

[0318] In some embodiments, the lateral dimension of the green LED structure is substantially the same as the lateral dimension of the red LED structure. In some embodiments, the first LED structure, e.g., the red LED structure and the second LED structure, e.g. the green LED structure, have the same central axis when the extended portions, such as **464** and **466**, are excluded. In some embodiments, the first LED structure and the second LED structure are aligned along the same central axis when the extended portions, such as **464** and **466**, are excluded.

[0319] In some embodiments, the bonding layer **460**, is used to bond the green LED structure and the blue LED structure together. In some embodiments, the bonding layer **456** is not transparent to the light emitted from the LED device **400**. In some embodiments, the materials and the thickness of the bonding layer **460** is the same as described above for the metal bonding layer **408**. In some embodiments, the bonding layer **460** can also be used as a reflector to reflect light emitted from the

LED structures above.

[0320] In some embodiments, when vertical transmission is used, the bonding layer **460** is transparent to the light emitted from the LED device **400**. In some embodiments, the bonding layer **460** is made of dielectric materials such as solid inorganic materials or plastic materials same as described above for the bonding layer **456**. In some embodiments, the transparent bonding layers can facilitate the light emitted from the layers below the bonding layers to pass through.

[0321] In some embodiments, a conductive layer **434** for electrode connection is formed at the bottom of the blue LED light emitting layer **436**. In some embodiments, the conductive layer **434** is a conductive transparent layer **434**, such as an ITO layer, that is formed between the blue LED light emitting layer **436** and the bonding layer **460** to improve conductivity and transparency. In some embodiments, as shown in FIG. **4A** and not shown in FIG. **4B**, the blue LED structure has a P-electrode contact pad **452** electrically connected to the blue LED light emitting layer **436**. In some embodiments, the P-electrode contact pad **452** is connected to the conductive layer **434**. In some embodiments, the P-electrode contact pad **452** is also connected to some P-electrode contact components (not shown in FIGS. **4A** and **4B**), similar to **422** and **424**, within the planarized insulation layers **454** and **458**, and within the transparent bonding layers **456** and **460**. Those P-electrode contact components are connected to a driver circuit **406**.

[0322] In some embodiments, a conductive layer **438** for electrode connection is formed at the top of the blue LED light emitting layer **436**. In some embodiments, the conductive layer **438** is a conductive transparent layer **438**, such as an ITO layer, that is formed between the blue LED light emitting layer **436** and an N-electrode **440** to improve conductivity and transparency. In some embodiments, as shown in FIG. **4B**, the N-electrode **440** has the N-electrode contact pads **442** and **444** electrically connected to the blue LED light emitting layer **436** through the N-electrode **440** and the conductive layer **438**. In some embodiments, the N-electrode **440** is also electrically connected to the N-electrode contact pad **420** of the green LED structure. In some embodiments, the N-electrode **440** is made of materials such as graphene, ITO, AZO, or FTO, or any combinations thereof.

[0323] In some embodiments, the lateral dimension of the blue LED light emitting layer **436** is substantially the same as the lateral dimension of the green LED light emitting layer **430**, especially for the effective light emitting area.

[0324] In some embodiments, a reflective layer **435** is positioned below the blue LED light emitting layer **436** between the conductive layer **434** and the bonding layer **460**. In some embodiments, an optional reflective layer **439** (not shown in FIG. **4B**) is positioned above the blue LED light emitting layer **436** on top of the conductive layer **438**.

[0325] In one approach, the blue LED light emitting layer **436** is grown on a separate substrate (referred to as the epitaxy substrate). The epitaxy substrate is then removed after bonding, for example, by a laser lift-off process or wet chemical etching, leaving the structure shown in FIG. **4B**.

[0326] In some embodiments, the blue LED light emitting layer **436** is for forming blue micro LEDs. Examples of a blue LED light emitting layer include III-V nitride, III-V arsenide, III-V phosphide, and III-V antimonide epitaxial structures. In some instances, films within the blue LED light emitting layer **436** can include the layers of P-type GaN/InGaN light-emitting layer/N-type GaN. In some embodiments, P type is generally Mg-doped, and N-type is generally Si-doped. In some examples, the thickness of the blue LED light emitting layer is about 0.1 micron to about 5 microns. In a preferred embodiment, the thickness of the blue LED light emitting layer is about 0.3 micron.

[0327] In some embodiments, the blue LED structure includes the reflective layer **435**, the conductive layer **434**, the blue LED light emitting layer **436**, the conductive layer **438**, and the optional reflective layer **439**. In some embodiments, the blue LED structure is formed within a planarized insulation layer **462**. In some embodiments, the planarized insulation layer **462** covers

the whole blue LED structure. In some embodiments, the whole blue LED structure is embedded within the planarized insulation layer **462**. In some embodiments, the bottom surface of the planarized insulation layer **462** is smoothed or planarized by the method of chemical mechanical polishing.

[0328] In some embodiments, vias or through holes are formed within the planarized insulation layer **462** and the transparent bonding layer **460** to accommodate a portion of the N-electrode **440** to connect to the N-electrode contact pad **420** of the green LED structure.

[0329] In some embodiments, the N-electrode **440** covers the top of the planarized insulation layer **462**. In some embodiments, the N-electrode **440** covers the top of the tri-color LED device **400**. In some embodiments, the N-electrode **440** connects to an N-electrode in an adjacent tri-color LED device (not shown in FIG. **4A** or **4B**) via the N-electrode contact pads **442** and **444**, and therefore serves as a common electrode.

[0330] In some embodiments, the lateral dimension of the blue LED structure is substantially the same as the lateral dimension of the green LED structure. In some embodiments, the second LED structure, e.g., the green LED structure and the third LED structure, e.g. the blue LED structure, have the same central axis when the extended portions, such as **466**, are excluded. In some embodiments, the second LED structure and the third LED structure are aligned along the same central axis when the extended portions, such as **466**, are excluded.

[0331] In some embodiments, the thickness of each of the conductive layers **410**, **414**, **428**, **432**, **434**, and **438** is about 0.01 micron to about 1 micron. In some instances, before any bonding process with the next epitaxial layer, each of the conductive layers **410**, **414**, **428**, **432**, **434**, and **438** is deposited on the respective corresponding epitaxial layer commonly by vapor deposition, for example, electron beam evaporation or sputtering deposition. In some examples, conductive layers are used to maintain a good conductivity for electrode connection while in some instances, improving optical properties of the LED devices, such as reflectivity or transparency.

[0332] In some embodiments, in order to improve the light emission efficiency from the tri-color LED device **400**, optical isolation structures such as **446** and **448** are formed along the sidewall of the tri-color LED device **400**. In some embodiments, the optical isolation structures **446** and **448** are made from dielectric materials such as SiO<sub>2</sub>.

[0333] As shown in FIG. **4A** from the top view, in some embodiments, the tri-color LED device **400** has a circular shape. In some embodiments, the optical isolation structures, such as **446** and **448**, are connected as one piece and formed as a circular sidewall around the tri-color LED device **400**. In some embodiments, the optical isolation structures are formed as a reflective cup as described in further detail below. In some embodiments, the three stacked LED structures within the tri-color LED device **400** are also in circular shapes. In some embodiments, the tri-color LED device **400** can be in other shapes, such as rectangle, square, triangle, trapezoid, polygon. In some embodiments, the optical isolation structures, such as **446** and **448**, are connected as one piece and formed as a sidewall around the tri-color LED device **400** with other shapes such as rectangle, square, triangle, trapezoid, polygon.

[0334] As shown in FIG. **4B**, in some embodiments, the red LED light emitting layer **412**, the green LED light emitting layer **430** and the blue LED light emitting layer **436** has oblique side surfaces. As used here, the oblique side surface may refer to a surface that is not perpendicular to the top or bottom surfaces of the respective LED light emitting layer. In some embodiments, the angle between the oblique sidewall and the bottom surface of the respective LED light emitting layer is less than 90 degrees. In some embodiments, the metal bonding layer **408** also has an oblique side surface. The oblique side surfaces may enhance easy connections for different connectors to the LED light emitting layers, prevent disconnections of those connectors because of sharp angles, and enhance the overall stability of the device.

[0335] In some embodiments, the light transmission efficiency of the multi-color LED device changes as the angle of the oblique side surface of the LED light emitting layers relative to a



normal line to the surface of the substrate **404** changes. In some embodiments, the light transmission efficiency of the multi-color LED device increases as the angle of the oblique side surface of the LED light emitting layers relative to a normal line to the surface of the substrate **404** increases. For example, when the angle of the side surface of the LED light emitting layers relative to the normal line to the surface of the substrate **404** is  $\pm 5$  degrees and when the optical isolation structures such as **446**, and/or **448** are not reflective cups as described below, the light emission efficiency of a multi-color LED device is 0.32%. For example, when the angle of the side surface of the LED light emitting layers relative to the normal line to the surface of the substrate **404** is  $\pm 15$  degrees and when the optical isolation structures such as **446**, and/or **448** are not reflective cups as described below, the light emission efficiency of a multi-color LED device is 2.7%. For example, when the angle of the side surface of the LED light emitting layers relative to the normal line to the surface of the substrate **404** is at (for example, when the light emitting layer is tilted) or very close to  $\pm 90$  degrees and when the optical isolation structures such as **446**, and/or **448** are not reflective cups as described below, the light emission efficiency of a multi-color LED device is equal to or very close to 56.4%.

[0336] In contrast, the implementation of reflective cup structures, as described in further detail below, improves the light transmission efficiency of the multi-color LED device. For example, when the angle of the side surface of the LED light emitting layers relative to the normal line to the surface of the substrate **404** is  $\pm 5$  degrees and when the optical isolation structures such as **446**, and/or **448** are reflective cups as described below, the light emission efficiency of a multi-color LED device is 0.65%, that is an increase of 104.6% compared with the LED device without a reflective cup. For example, when the angle of the side surface of the LED light emitting layers relative to the normal line to the surface of the substrate **404** is  $\pm 15$  degrees and when the optical isolation structures such as **446**, and/or **448** are reflective cups as described below, the light emission efficiency of a multi-color LED device is 6.65%, that is an increase of 144.4% compared with the LED device without a reflective cup. For example, when the angle of the side surface of the LED light emitting layers relative to the normal line to the surface of the substrate **404** is at (for example, when the light emitting layer is tilted) or very close to  $\pm 90$  degrees and when the optical isolation structures such as **446**, and/or **448** are reflective cups as described below, the light emission efficiency of a multi-color LED device is equal to or very close to 66.65%, that is an increase of 18.4% compared with the LED device without a reflective cup.

[0337] In some embodiments, the size of the red LED light emitting layer **412**, the green LED light emitting layer **430** and the blue LED light emitting layer **436** are similar. For example, the surface areas of the red LED light emitting layer **412**, the green LED light emitting layer **430** and the blue LED light emitting layer **436** are substantially the same, especially for the effective light emitting areas.

[0338] In some embodiments, reflective layers are formed above and below each of the LED light emitting layers to improve light transmission efficiency. As shown in FIG. **4B**, in some embodiments, a reflective layer **409** is formed between the bonding layer **408** and the red LED light emitting layer **412**. In some embodiments, the reflective layer **409** is formed between the bonding layer **408** and the conductive layer **410** when the conductive layer **410** is present. In some embodiments, a reflective layer **415** is formed between the bonding layer **456** (or/and within the planarized insulation layer **454**), and the red LED light emitting layer **412**. In some embodiments, a reflective layer **415** is formed between the bonding layer **456** (or/and within the planarized insulation layer **454**), and the conductive layer **414** when the conductive layer **414** is present.

[0339] In some embodiments, a reflective layer **427** is formed between the bonding layer **456** (or/and within the planarized insulation layer **458**), and the green LED light emitting layer **430**. In some embodiments, reflective layer **427** is formed between the bonding layer **456** (or/and within the planarized insulation layer **458**), and the conductive layer **428** when the conductive layer **428** is present. In some embodiments, a reflective layer **433** is formed between the bonding layer **460**

(or/and within the planarized insulation layer **458**), and the green LED light emitting layer **430**. In some embodiments, the reflective layer **433** is formed between the bonding layer **460** (or/and within the planarized insulation layer **458**), and the conductive layer **432** when the conductive layer **432** is present.

[0340] In some embodiments, a reflective layer **435** is formed between the bonding layer **460** (or/and within the planarized insulation layer **462**), and the blue LED light emitting layer **436**. In some embodiments, the reflective layer **435** is formed between the bonding layer **460** (or/and within the planarized insulation layer **462**), and the conductive layer **434** when the conductive layer **434** is present. In some embodiments, an optional reflective layer **439** (not shown in FIG. **4B**) is formed between the N-electrode pad **440** and the blue LED light emitting layer **436**, while still allowing the blue LED light emitting layer **436** to be electrically connected to the N-electrode pad **440**, for example, through a conductive path. In some embodiments, the optional reflective layer **439** is formed between the N-electrode pad **440** and the conductive layer **438** when the conductive layer **438** is present, while still allowing the conductive layer **438** to be electrically connected to the N-electrode pad **440**, for example, through a conductive path.

[0341] In some embodiments, the materials, composition, properties and fabrication of the reflective layers are the same as described above with respect to FIGS. **1-3**.

[0342] In some embodiments, through dry etching and wet etching, a tri-color LED structure is formed and the axes of LED structures of different colors are aligned with one another vertically. In some embodiments, the LED structures of different colors share the same axis.

[0343] In some embodiments, each of the LED structures of different colors form a pyramid like shape or a trapezoidal cross-sectional shape within its respective planarized insulation structure. Each layer has a narrower width or smaller area compared to a layer beneath it. In this instance, the width or area is measured by the dimensions of a plane parallel to the surface of the substrate **404**. In some embodiments, especially when planarized layered structures are used, each of the LED structures of different colors has substantially the same lateral dimension compared with other LED structures. When each of the LED structures have substantially the same area, the light emitting efficiency from the whole LED device is improved.

[0344] In some embodiments, especially when planarized layered structures are not used and each of the LED structures of different colors are bonded together by bonding layers that only cover the area of the LED structures without extension beyond the area of the LED structures, the whole multi-color LED device, forms a pyramid (or inverted cone) like shape or a trapezoidal cross-sectional shape (not shown in FIG. **4B**). In some embodiments, the lateral dimension of the bottom LED structure, for example, the red LED structure, can be the longest, and the lateral dimension of the top LED structure, for example, the blue LED structure, can be the shortest. A pyramid like shape can be formed naturally when each of the layers within the LED device is etched and patterned from bottom up. A pyramid like structure can improve the electronic connections between the individual LED structures and to the electrodes, and simplify the fabrication process. For example, the electrode connections are exposed in each layer for easy connection.

[0345] In some embodiments, the bottom layer such as the metal bonding layer **408** has a lateral dimension of about 1 micron to about 500 microns. In a preferred embodiment, the lateral dimension of the metal bonding layer **408** at the bottom of the multi-color LED device is about 2.0 microns. In some embodiments, the vertical height of the multi-color LED device is about 1 micron to about 500 microns. In a preferred embodiment, the vertical height of the multi-color LED device is about 1.9 microns. In a preferred embodiment, the lateral dimension of the conductive layer **438** at the top of the multi-color LED device is about 1.0 micron.

[0346] In some embodiments, the aspect ratio of a cross section of a layer of the tri-color LED device remains substantially the same when the lateral dimension of the same layer varies. For example, when the lateral dimension of a patterned epitaxial layer is 5 microns, the thickness of the patterned epitaxial layer is less than a micron. In another example, when the lateral dimension of

the same patterned epitaxial layer increases, the thickness of the same patterned epitaxial layer increases accordingly to maintain the same aspect ratio. In some embodiments, the aspect ratio of the cross-section of the epitaxial layers and other layers is less than 1/5 in thickness/width.

[0347] The shape of the LED device is not limited and in some other embodiments, the cross-sectional shape of the tri-color LED device can take the form of other shapes, for example, a reverse trapezoid, a semi-oval, a rectangle, a parallelogram, a triangle, or a hexagon, etc.

[0348] In some embodiments, with the planarized insulation layers, such as **454**, **458** and **462**, covering each of the LED structures of different colors, the fabrication process for the single pixel tri-color LED device is simplified and the light emission efficiency of the single pixel tri-color LED device is improved. For example, each of the LED structures of different colors can form on its own including the conductive layers, reflective layers and the electrode contact pads and their related connections within the respective planarized insulation layer first, then the LED structures are bonded together with the respective bonding layer.

[0349] In contrast, in a process to fabricate a directly stacked tri-color LED device without planarization, where the LED structures of different colors are bonded together with some bonding layers directly, the single pixel tri-color LED device may be a pyramid (or inversed cone) like shape or a trapezoidal cross-sectional shape as a result of the layer by layer patterning (and/or etching). Thus, the effective light emitting area for an LED structure at the bottom of the stack of the single pixel tri-color LED device is the biggest while the effective light emitting area for an LED structure at the top of the stack is the smallest. The unevenness of the light emitting regions among the multiple LED structures within the LED device can degrade its light emission efficiency. While with the planarized layered structure, since each of the LED structures is fabricated within its own planarized insulation layer, the single pixel tri-color LED device are not limited to a pyramid structure as described above. Instead, the effective light emitting area of the different LED structures within the single pixel tri-color LED device can be adjusted according to the design. In some instance, the horizontal effective light emitting areas of the different LED structures within the single pixel tri-color LED device are substantially the same to improve the light emission efficiency and easiness for electrical connections. In some cases, compared with a similar tri-color LED structure without planarization, the planarized tri-color LED structure can improve light emission efficiency by at least 5%, at least 10% or sometimes, at least 20%.

[0350] In some embodiments, when a respective epitaxy substrate is used to grow each of the LED light emitting layers as described above, an insulation layer can be deposited on each of the epitaxy substrate covering the corresponding LED light emitting layers and other layers such as the conductive layers and reflective layers first. A planarization process is then followed to even the surface of the insulation layer that embeds the respective LED structure. Vias for electrical connections are also formed within the planarized layers before bonding.

[0351] In another embodiment, the layers of an LED structure including the bonding layer can be formed on a planarized insulation layer that already embeds a formed LED structure directly, followed by the formation of the planarized insulation layer to cover the current LED structure. Vias for electrical connections are also formed within the planarized layer before the next LED structure is formed above the current LED structure.

[0352] Compared with some other processes without planarized insulation layers, where the bonding layer contacts the top or bottom of the LED structure directly in order to form a device, the bonding layer can contact with the planarized insulation layer without touching the LED structures. Thus the features and layers within each of the planarized LED structures are better protected and less susceptible to the outside destruction force. Furthermore, the planarized surface can improve the light transmission efficiency by reducing deflection from an uneven surface.

[0353] In some embodiments, the top conductive layer **438** above the third LED light emitting layer **436** is patterned using photolithography and etching. In some instances, the etching method used to form the pattern is dry etching, for example, inductively coupled plasma (ICP) etching, or

wet etching with an ITO etching solution. In some embodiments, the same patterning methods can apply to all the other conductive layers, including layers **410**, **414**, **428**, **432**, **434**, and **438** within the tri-color LED device **400**.

[0354] In some embodiments, the blue LED light emitting layer **436** and the green LED light emitting **430** are patterned using photolithography and etching. In some instances, the etching method used to form the pattern is dry etching, for example, inductively coupled plasma (ICP) etching, with Cl<sub>2</sub> and BCl<sub>3</sub> etching gases.

[0355] In some embodiments, the bonding layers including **460** and **456** are patterned using photolithography and etching. In some instances, the etching method used to form the pattern is dry etching, for example, inductively coupled plasma (ICP) etching, with CF<sub>4</sub> and O<sub>2</sub> etching gases.

[0356] In some embodiments, the reflective layers including **409**, **415**, **427**, **433**, **435** and **439** are patterned using photolithography and etching. In some instances, the etching method used to form the pattern for the reflective layers especially the DBR layers is dry etching, for example, inductively coupled plasma (ICP) etching, with CF<sub>4</sub> and O<sub>2</sub> etching gases, or ion beam etching (IBE) with Ar gas.

[0357] In some embodiments, the red LED light emitting layer **412** is patterned using photolithography and etching. In some instances, the etching method used to form the pattern is dry etching, for example, inductively coupled plasma (ICP) etching, with Cl<sub>2</sub> and HBr etching gases.

[0358] In some embodiments, the metal bonding layer **408** is patterned using photolithography and etching. In some instances, the etching method used to form the pattern is dry etching, for example, inductively coupled plasma (ICP) etching, with Cl<sub>2</sub>/BCl<sub>3</sub>/Ar etching gases, or ion beam etching (IBE) with Ar gas.

[0359] In some embodiments, after each of the LED device structures is patterned, an insulation layer, such as **454**, **458**, **462**, is deposited on the surface of the patterned LED structure including all the patterned layers, side walls, and the exposed substrate. In some embodiments, the insulation layer is made of SiO<sub>2</sub> and/or Si<sub>3</sub>N<sub>4</sub>. In some embodiments, the insulation layer is made of TiO<sub>2</sub>. In some embodiments, the insulation layer is formed with composition similar to SiO<sub>2</sub> after curing a layer such as SOG at a high temperature. In some embodiments, the insulation layer is made of a material that has a similar thermal coefficient of the layers underneath the insulation layer. The surface of the insulation layer is then smoothed or planarized by a relevant method understood by a person of ordinary skill in the art, such as chemical mechanical polishing.

[0360] In some embodiments, the insulation layer after planarization is patterned to expose the electrode contact area using photolithography and etching. In some instances, the etching method used to form the pattern is dry etching, for example, inductively coupled plasma (ICP) etching, with CF<sub>4</sub> and O<sub>2</sub>.

[0361] In some embodiments, P-electrode or anode metal pads are vapor deposited, or by other deposition method, on a suitable location of the patterned LED structure, such as on one side and/or in vias within the planarized insulation layer, to electrically connect the red LED structure, the green LED structure, and the blue LED structure.

[0362] In some embodiments, separate N-electrode or cathode metal pads are vapor deposited, or by other deposition method, on a suitable location of the patterned LED structure, such as on one side/top and/or in vias within the planarized insulation layer, to electrically connect the red LED structure, the green LED structure, and the blue LED structure.

[0363] FIG. **5** is a cross-sectional view of a single pixel tri-color LED device **500** along the diagonal line **102** in FIG. **1A** with a refractive structure, in accordance with some embodiments. In some embodiments, although not all shown in FIG. **5**, the single pixel tri-color LED device **500** has similar structures as any one of the single pixel tri-color LED devices shown in FIGS. **1-4** with the addition of a refractive structure **502** formed above the top surface of the single pixel tri-color LED device to improve light emission efficiency. Light emitted from the single pixel tri-color LED device is emitted out through a top surface of the single pixel tri-color LED device without the

refractive structure (the light emitting out area). In some embodiments, the top surface of the refractive structure **502** is planarized. In some embodiments, the refractive structure **502** covers and is in contact with the exposed surface of the top electrode, such as the N-electrode **140**. In some embodiments, the refractive structure **502** is formed directly on the surface of the planarized insulation layer **176**. In some embodiments, the refractive structure **502** is the same as the planarized insulation layer **176** and integrated with the planarized insulation layer **176**.

[0364] In some embodiments, the refractive structure **502** is formed between the optical isolation structures, for example, a reflective cup, such as **146** and **148** and the top surface of the single pixel tri-color LED device without the refractive structure, i.e., the light emitting out area. In some embodiments, the top surface of the refractive structure **502** is above the top of the optical isolation structures. In some embodiments, the top surface of the refractive structure **502** is the same or below the top of the optical isolation structures. In some embodiments, the top surface of the refractive structure is above the top electrode, such as the N-electrode **140**. In some embodiments, the top surface of the refractive structure is the same or below the top electrode, such as the N-electrode **140**.

[0365] In some embodiments, the refractive structure **502** changes the light path emitted from the single pixel tri-color LED device by either making the light emitted from the LED device more focused or more divergent according to the design needs.

[0366] In some embodiments, the refractive layer **502** is made of dielectric materials. In some embodiments, the dielectric material is transparent to the light emitted by the single pixel tri-color LED device, such as silicon oxide, silicon nitride, silicon carbide, titanium oxide, zirconium oxide, aluminum oxide, etc. In some embodiments, the dielectric material is selected from one or more polymers such as SU-8, photosensitive polyimide (PSPI), BCB, etc.

[0367] In some embodiments, the refractive layer **502** is formed directly above the planarized insulation layers. In some embodiments, the refractive layer **502** is formed by deposition, sputtering, or other methods.

[0368] FIG. **6A** is a cross-sectional view of a single pixel tri-color LED device **600** along the diagonal line **102** in FIG. **1A** with a micro-lens above a reflective structure, in accordance with some embodiments.

[0369] FIG. **6B** is a cross-sectional view of a single pixel tri-color LED device **600** along the diagonal line **102** in FIG. **1A** with a micro-lens within the area formed by a reflective structure, in accordance with some embodiments.

[0370] In some embodiments, although not all shown in FIGS. **6A-6B**, the single pixel tri-color LED device **600** has similar structures as any one of the single pixel tri-color LED devices shown in FIGS. **1-5** with the addition of a micro-lens **602** formed above the top surface of the single pixel tri-color LED device to improve light emission efficiency. Light emitted from the single pixel tri-color LED device is emitted out through the top surface of the single pixel tri-color LED device without the micro-lens structure (the light emitting out area). In some embodiments, the micro-lens **602** is formed directly on the surface of the planarized insulation layer **176**. In some embodiments, the micro-lens **602** is formed directly on the surface of the refractive structure **502** as shown in FIG. **5**. In some embodiments, the micro-lens **602** covers and is in contact with the exposed surface of the top electrode, such as the N-electrode **140**.

[0371] In some embodiments, an optional spacer **604** is formed on top of the light emitting out area at the bottom of the micro-lens **602**. In some embodiments, the top surface of the spacer **604** is planarized. In some embodiments, the spacer **604** is formed directly on the surface of the planarized insulation layer **176**. In some embodiments, the spacer **604** is formed directly on the surface of the refractive structure **502** as shown in FIG. **5**. In some embodiments, the spacer **604** is the same as the refractive structure **502** as shown in FIG. **5** and integrated with the refractive structure **502**. In some embodiments, the spacer **604** covers and is in contact with the exposed surface of the top electrode, such as the N-electrode **140**. In some embodiments, the spacer **604** is

integrated with the micro-lens **602**. In some embodiments, the spacer **604** is the same as the planarized insulation layer **176** and integrated with the planarized insulation layer **176**.

[0372] In some embodiments, the micro-lens **602** is formed between the optical isolation structures, for example, a reflective structure or a reflective cup, such as **146** and **148** and the top surface of the single pixel tri-color LED device between the optical isolation structures without the micro-lens, i.e., the light emitting out area. In some embodiments, the top surface of the micro-lens **602** is above the top of the optical isolation structures as shown in FIG. **6A**. When the top surface of the micro-lens **602** is above the top of the reflective structures, such as **146** and **148**, substantially all the light emitted from the single pixel tri-color LED device including the reflective cup can be captured and focused by the micro-lens **602**. In some embodiments, the top surface of the micro-lens **602** is the same or below the top of the optical isolation structures as shown in FIG. **6B**. When the top surface of the micro-lens **602** is below or at the same level as the top of the reflective structures, such as **146** and **148**, at least a portion of the light emitted from the micro-lens **602** is further reflected by the reflective structures or reflective cup which is confined in a certain area.

[0373] In some embodiments, the lateral dimension of the bottom of the micro-lens **602** is smaller than that of the light emitting out area. In some embodiments, the lateral dimension of the bottom of the micro-lens **602** is the same or greater than that of the light emitting out area. In some embodiments, the lateral dimension of the bottom of the micro-lens **602** is smaller than that of the top surface area of the top light emitting layer **136**. In some embodiments, the lateral dimension of the bottom of the micro-lens **602** is the same or greater than that of the top surface area of the top light emitting layer **136**.

[0374] In some embodiments, the optional spacer **604** is formed between the optical isolation structures, for example, a reflective cup, such as **146** and **148** and the top surface of the single pixel tri-color LED device without the micro-lens and the spacer, i.e., the light emitting out area. In some embodiments, the top surface of the spacer **604** is above the top of the optical isolation structures. In some embodiments, the top surface of the spacer **604** is the same or below the top of the optical isolation structures. In some embodiments, the top surface of the spacer **604** is above the top electrode, such as the N-electrode **140**. In some embodiments, the top surface of the spacer **604** is the same or below the top electrode, such as the N-electrode **140**. In some embodiments, the lateral dimension of the bottom of the micro-lens **602** is smaller than that of the top surface of the spacer **604**. In some embodiments, the lateral dimension of the bottom of the micro-lens **602** is the same or greater than that of the top surface of the spacer **604**.

[0375] In some embodiments, the micro-lens **602** changes the light path emitted from the single pixel tri-color LED device by making the light emitted from the LED device more focused or more divergent according to the design needs.

[0376] In some embodiments, the spacer **604** extends the light path emitted from the single pixel tri-color LED device. In some embodiments, the spacer **604** changes the light path emitted from the single pixel tri-color LED device by making the light emitted from the LED device more focused or more divergent according to the design needs.

[0377] In some embodiments, the micro-lens **602** can be made from a variety of materials that are transparent at the wavelengths emitted from the single pixel tri-color LED device. Example transparent materials for the micro-lens **602** include polymers, dielectrics and semiconductors. In some embodiments, the dielectric materials include one or more materials, such as silicon oxide, silicon nitride, silicon carbide, titanium oxide, zirconium oxide, aluminum oxide, etc. In some embodiments, the micro-lens **602** is made of photoresist.

[0378] The spacer **604** is an optically transparent layer that is formed to maintain the position of the micro-lens **602** relative to the pixel light source, such as the single pixel tri-color LED device, underneath it. The spacer **604** can be made from a variety of materials that are transparent at the wavelengths emitted from the pixel light source. Example transparent materials for the spacer **604** include polymers, dielectrics and semiconductors. In some embodiments, the dielectric materials

include one or more materials, such as silicon oxide, silicon nitride, silicon carbide, titanium oxide, zirconium oxide, aluminum oxide, etc. In some embodiments, the spacer **604** is made of photoresist. In some embodiments, the spacer **604** and the microlens **602** have the same material. In some embodiments, the spacer **604** and the microlens **602** have different materials.

[0379] In some embodiments, the height of the micro-lens **602** is not more than 2 micrometers. In some embodiments, the height of the micro-lens **602** is not more than 1 micrometers. In some embodiments, the height of the micro-lens **602** is not more than 0.5 micrometers. In some embodiments, the width of the micro-lens **602** is not more than 4 micrometers. In some embodiments, the width of the micro-lens **602** is not more than 3 micrometers. In some embodiments, the width of the micro-lens **602** is not more than 2 micrometers. In some embodiments, the width of the micro-lens **602** is not more than 1 micrometers. In some embodiments, the ratio of the width and the height of the micro-lens **602** is more than 2.

[0380] In some embodiments, the shape of the micro-lens **602** is generally hemisphere. In some embodiments, the center axis of the micro-lens **602** is aligned with or the same as the center axis of the lens-less single pixel tri-color LED device.

[0381] For clarity, FIGS. **6A-6B** show in some embodiments, in a display panel, each of single pixel light sources such as the tri-color LED device corresponds to one single micro-lens **602**. It should be understood that a full display panel includes an array of many individual pixels and many micro-lenses. In addition, it may not have to be a one to one correspondence between micro-lenses and pixel light sources, nor a one to one correspondence between the pixel driver circuits (not shown) and the pixel light sources. Pixel light sources could also be made of multiple individual light elements, for example, single pixel LEDs connected in parallel. In some embodiments, one micro-lens **602** can cover several lens-less single pixel tri-color LED device.

[0382] The individual micro-lens **602** has a positive optical power and is positioned to reduce the divergence or viewing angle for light that is emitted from the corresponding pixel light source. In one example, the light beam emitted from the pixel light source has an original divergence angle that is fairly wide. In one embodiment, the original angle for the edge light ray of the light beam relative to a vertical axis orthogonal to the substrate **104** is greater than 60 degrees. The light is bent by the micro-lens **602**, so that the new edge light ray now has a reduced divergence angle. In one embodiment, the reduced angle is less than 30 degrees. The micro-lenses in the micro-lens array are typically the same. Examples of micro-lenses include spherical micro-lenses, aspherical micro-lenses, Fresnel micro-lenses and cylindrical micro-lenses.

[0383] The micro-lens **602** typically has a flat side and a curved side. In FIG. **6**, the bottom of the micro-lens **602** is the flat side, and the top of the micro-lens **602** is the curved side. Typical shapes of the base of each micro-lens **602** include circle, square, rectangle, and hexagon. The individual micro-lenses in a micro-lens array of a display panel may be the same or different: in shape, curvature, optical power, size, base, spacing, etc. In some embodiments, the micro-lens **602** conforms to the shape of the single pixel tri-color LED device. In one example, the shape of the base of the micro-lens **602** is the same as that of the single pixel tri-color LED device, for example, in FIGS. **6A-6B**, they are both circular. In another example, the shape of the base of the micro-lens **602** is not the same as that of the single pixel tri-color LED device, for instance, the circular base of micro-lens has a same width as the single pixel tri-color LED, but a smaller area since the micro-lens base is a circle and the base of the single pixel tri-color LED is a square. In some embodiments, the micro-lens base area is the smaller than the area of the pixel light source. In some embodiments, the micro-lens base area is the same or larger than the area of the pixel light source.

[0384] In some embodiments, where the micro-lens **602** is formed, the spacer layer **604** can be formed with the micro-lens **602** in the same process with the same material. In some embodiments, the height of the pixel light source is larger than, the same, or smaller than the thickness of the spacer **604** measured from the bottom of the substrate **104**.

[0385] The thickness of the spacer **604** is designed to maintain the proper spacing between the micro-lens **604** and the pixel light source. As one example, for a spacer that maintains an optical spacing between pixel light source and micro-lens that is more than a focal length of the micro-lens, an image of a single pixel is formed at a certain distance. As another example, for an optical spacer that maintains an optical spacing between pixel light source and micro-lens that is less than a focal length of the micro-lens, a reduced divergence/viewing angle is achieved. The amount of reduction of divergence/viewing angle also partly depends on the thickness of the spacer **604** measured from the top surface of the pixel light source. In some embodiments, the thickness of the spacer **604** measured from the top surface of the pixel light source is not more than 1 micrometer. In some embodiments, the thickness of the spacer **604** measured from the top surface of the pixel light source is not more than 0.5 micrometer. In some embodiments, the thickness of the spacer **604** measured from the top surface of the pixel light source is not more than 0.2 micrometer. In some embodiments, the thickness of the spacer **604** measured from the top surface of the pixel light source is about 1 micrometer.

[0386] In some embodiments, a brightness enhancement effect is achieved via integrating a micro-lens array onto the display panel. In some examples, the brightness with the micro-lens array is 4 times the brightness without the micro-lens array in the direction perpendicular to the display surface, due to light concentrating effect of micro-lenses. In alternative embodiments, the brightness enhancement factor can vary according to different designs of the micro-lens array and the optical spacer. For example, a factor greater than 8 can be achieved.

[0387] In some embodiments, a first method for fabricating a micro-lens includes a step of depositing a micro-lens material layer directly on at least the top of the pixel light source and in direct physical contact with the pixel light source. In some embodiments, the shape of the micro-lens material layer is conformed to the shape of the pixel light source and forms a hemisphere on the pixel light source. In some embodiments, the top of the pixel light source is generally flat and the shape of the formed micro-lens **602** is generally hemispheric. In some embodiments, the micro-lens material layer is deposited on the surface of the pixel light source, such as the planarized surface of the single pixel tri-color LED device, directly by chemical vapor deposition (CVD) technology. In some embodiments, the deposition parameters for the CVD process are: the power is about 0 W to about 1000 W, the pressure is about 100 milli-torr to about 2000 milli-torr, the temperature is around 23° C. to around 500° C., the gas flow is about 0 to about 3000 sccm (standard cubic centimeters per minute), and the time is about 1 hour to about 3 hours. In some embodiments, the material of the micro-lens material layer is a dielectric material such as silicon dioxide.

[0388] In some embodiments, the first method for fabricating a micro-lens further includes a step of patterning the micro-lens material layer to expose the electrode area of the substrate. In some embodiments, the step of patterning the micro-lens material layer includes an etching step. In some embodiments, the etching step includes a step of forming a mask on the surface of the micro-lens material. The etching step also includes a step of patterning the mask via a photolithography process, thereby forming openings in the mask and exposing the micro-lens material layer above the electrode area of the pixel light source. The etching step further includes a step of etching the portions of the micro-lens material layer exposed by the openings with the mask protection in place. In some embodiments, the exposed micro-lens material layer is etched by a wet etching method.

[0389] In some embodiments, a second method for fabricating a micro-lens also includes an optional step of forming a mark layer with marks for aligning to the micro-lens material layer deposited in later steps. For example, the mark layer is formed to align the units of the light emitting pixels to the micro-lens material layer in order to form the micro-lens at the center of the pixel light source. In some embodiments, the mark layer is formed to align the pixel light source to the layers above it especially the micro-lens material layer in order to form the micro-lens on the



top of the pixel light source.

[0390] The second method for fabricating a micro-lens further includes a step of depositing a micro-lens material layer directly on at least the top of one pixel light source. FIGS. **6C-6D** further show a fabrication method to form a display panel integrated with a micro-lens array using top down pattern transfer, according to some embodiments. In some embodiments, the micro-lens material layer **645** covers the top of the pixel light source **606M** as shown in FIG. **6C** and the top surface of the micro-lens material layer **645** is flat. In some embodiments, the micro-lens material layer **645** is deposited on the top of the pixel light source array **606** by spin coating. In some embodiments, the material of the micro-lens material layer **645** is photoresist. In some embodiments, the material of the micro-lens material layer **645** is dielectric material such as silicon oxide.

[0391] The second method for fabricating a micro-lens further includes a step of patterning the micro-lens material layer from the top down, thereby forming at least a hemisphere in the micro-lens material layer as shown in FIGS. **6C-6D**. In some embodiments, the patterning is carried out without passing through or etching to the bottom of the micro-lens material layer **645**. In some embodiments, the hemisphere of the micro-lens **620** is placed above at least one pixel light source **606M**.

[0392] In some embodiments, the step of patterning the micro-lens material layer from the top down further includes a first step of depositing a mask layer **630** on the surface of the micro-lens material layer **645** as shown in FIG. **6C**.

[0393] The step of patterning the micro-lens material layer from the top down also includes a second step of patterning the mask layer **630** to form a hemisphere pattern in the mask layer **630**. In some examples, the mask layer **630** is patterned by a photolithography process firstly and then a reflowing process. In some embodiments, the photo-sensitive polymer mask layer **630** is patterned into isolated cells **640**, as shown in FIG. **6C** in dotted rectangle cells, to prepare for the formation of the hemisphere pattern. As one example, the isolated cells **640** are patterned and formed via a photo-lithography process. The patterned photo-sensitive polymer mask layer **650** with the isolated cells **640** is then shaped into hemisphere pattern **660** using high temperature reflow process. In one approach, the isolated cells **640** are formed into isolated hemisphere pattern **660** via high temperature reflow. In some embodiments, the isolated hemisphere pattern **660** of one pixel is not in direct physical contact with a hemisphere pattern of an adjacent pixel. In some embodiments, the hemisphere pattern **660** of one pixel only contacts with a hemisphere pattern of an adjacent pixel at the bottom of the hemisphere pattern **660**. The patterned photo-sensitive polymer mask layer **650** is heated to a temperature above the melting point of the polymer material for a certain time. After the polymer material melts into a liquefied state, the surface tension of the liquefied material will render it into a shape with a smooth curvature surface. For a cell with a round base of a radius  $R$  when the height of the cell is  $2R/3$ , a hemispherical shape/pattern will be formed after the reflow process. FIG. **6C** shows a display panel integrated with the array of hemisphere patterns **660** after the high temperature reflow process is finished. In some embodiments, the hemisphere pattern in the mask layer can be formed by other fabrication method including the fabrication method for the micro-lens described in the first method for fabricating a micro-lens. In some other embodiments, the hemisphere pattern in the mask layer can be formed using grayscale mask photolithography exposure. In some other embodiments, the hemisphere pattern in the mask layer can be formed via a mold/imprinting process.

[0394] The step of patterning the micro-lens material layer from the top down further includes a third step of using the hemisphere pattern **660** as a mask, etching the micro-lens material layer **645** to form the hemisphere in the micro-lens material layer **645**. In some examples, etching the micro-lens material layer **645** is by a photolithography process. In some examples, etching the micro-lens material layer **645** is by a dry etching such as plasma etching process **635** as shown in FIG. **6C**. In some embodiments, after the micro-lens material layer **645** is etched, the micro-lens material layer

**645** is not etched through to expose the top surface of the pixel light source **606M** as shown in FIGS. **6C-6D**, thereby a spacer **670** is formed on the top of the pixel light source **606M** or covering the top of the pixel light source **606M** as shown in FIG. **6D**.

[0395] The second method for fabricating a micro-lens further includes a step of patterning the micro-lens material layer to expose the electrode area (not shown in FIG. **6D**) of the substrate. In some embodiments, the step of patterning the micro-lens material layer includes an etching step. In some embodiments, the etching step includes a step of forming a mask on the surface of the micro-lens material. The etching step also includes a step of patterning the mask via a photolithography process, thereby forming openings in the mask and exposing the micro-lens material layer above the electrode area of the pixel light source. The etching step further includes a step of etching the exposed micro-lens material layer with the mask protection. In some embodiments, the exposed micro-lens material layer is etched by a wet etching method. In some embodiments, the opening for an electrode is positioned outside the display array area.

[0396] As described above, FIGS. **6A** to **6D** show various fabrication methods to form a display panel integrated with a micro-lens array. It should be understood that these are merely examples, and other fabrication techniques can also be used.

[0397] Although the detailed description contains many specifics, these should not be construed as limiting the scope of the invention but merely as illustrating different examples and aspects of the invention. It should be appreciated that the scope of the invention includes other embodiments not discussed in detail above. For example, micro-lenses with different shape bases may also be used, such as square base or other polygon base.

[0398] FIG. **7** is a cross-sectional view **700** of three single pixel tri-color LED devices **710**, **720** and **730** along the diagonal line such as **102** in FIG. **1A** on a substrate **104**, in accordance with some embodiments. In some embodiments, although not all shown in FIG. **7**, each of the single pixel tri-color LED devices **710**, **720** and **730** has similar structures as any one of the single pixel tri-color LED devices shown in FIGS. **1-6**. The cross-sectional view for a single pixel tri-color LED device **710** within the rectangle **750** is equivalent to the cross sectional views as shown in any of the FIGS. **1-6** as described above.

[0399] In some embodiments, as shown in any of the embodiments in FIGS. **1-7**, the single pixel tri-color LED device further comprises one or more reflective cup structures, such as **702**, **704** and **706**. The reflective structures, such as **702**, **704** and **706** surrounds each of the single pixel tri-color LED devices **710**, **720** and **730**. The reflective cup may be formed on the semiconductor substrate **104** and positioned around the light emitting region where light from the single pixel tri-color LED device is emitted. For example, as shown in FIGS. **1A-1C**, from the cross-sectional view along the **102** direction in FIG. **1B**, and from the cross-sectional view along the **150** direction in FIG. **1C**, the reflective cup may include four reflective cup parts **146**, **148**, **170** and **172**. In some embodiments, the reflective cup parts **146**, **148**, **170** and **172** may be formed on the semiconductor substrate **104** and positioned around the light emitting region. In some embodiments, the reflective cup can isolate at least some of the light or substantially all the light emitted from the light emitting region. For example, as shown in FIGS. **1B-1C**, when a height of the reflective cup is higher than a height of the light emitting region, the reflective cup parts **146**, **148**, **170** and **172** can isolate the at least some of the light or substantially all the light emitted from the light emitting region. Therefore, the reflective cup can suppress the inter-pixel light crosstalk and improve the overall contrast of LED displays. The reflection from the reflective cup also increases the light emitting efficiency and brightness by focusing the light emission into a certain direction.

[0400] In some embodiments, the height of the reflective cup may be larger than a height of the bottom LED structure, such as the red LED structure, larger than a height of the middle LED structure, such as the green LED structure, or larger than a height of the top LED structure, such as the blue LED structure. In some embodiments, the total height of the reflective cup may be larger than a height of the combined height of the bottom LED structure, such as the red LED structure,

the middle LED structure, such as the green LED structure, and the top LED structure, such as the blue LED structure. In some embodiments, the total height of the reflective cup may be larger than the height of the single pixel tri-color LED device without the planarized layer. In some embodiments, the height of the reflective cup is between 0.5 micron to 50 microns. In some embodiments, the height of the reflective cup is between 1 micron to 20 microns. In some embodiments, the height of the reflective cup is between 2 microns to 10 microns. In a preferred embodiment, the height of the reflective cup is about 2.5 microns while the height of the single pixel tri-color LED device without the planarized layer is about 1.9 microns. Yet in some embodiments, the reflective cup parts **146**, **148**, **170** and **172** may have different heights. In some embodiments, the cross-section of a reflective cup part such as **146** or **148** is a triangle. In some embodiments, the cross-section of a reflective cup part such as **146** or **148** is a trapezoid with bottom edge longer than top edge. In some embodiments, the bottom width of the reflective cup part such as **146** or **148** is between 0.3 micron to 50 microns. In some embodiments, the bottom width of the reflective cup part such as **146** or **148** is between 0.5 micron to 25 microns. In a preferred embodiment, the bottom width of the reflective cup part such as **146** or **148** is about 1 micron. In some embodiments, the distance of the nearest edge of the bottom of the reflective cup part such as **146** or **148** to the nearest edge of bottom of the single pixel tri-color LED device, is between 0.2 micron to 30 microns. In some embodiments, the distance of the nearest edge of the bottom of the reflective cup part such as **146** or **148** to the nearest edge of bottom of the single pixel tri-color LED device, is between 0.4 micron to 10 microns. In a preferred embodiment, the distance of the nearest edge of the bottom of the reflective cup part such as **146/446** or **148/448** to the nearest edge of bottom of the single pixel tri-color LED device, such as the p-electrode connection structure **422** as shown in FIG. **4B**, is about 0.6 micron.

[0401] In some embodiments, the distance between the centers of the adjacent reflective cup part such as **146/446** and **148/448** of the single pixel tri-color LED device, is between 1 micron to 50 microns. In a preferred embodiment, the distance between the centers of the adjacent reflective cup part such as **146** and **148** of the single pixel tri-color LED device, is about 5 microns.

[0402] In some embodiments, a divergence angle of 0° may correspond to light propagating perpendicular to a top surface of the light emitting region, and a divergence angle of 90° may correspond to light propagating parallel to the top surface of the light emitting region. Changing the geometry of the reflective cup can control the divergence angle of the light emitting from the light emitting region. Therefore, the reflective cup may reduce the divergence of the light emitted from the light emitting region, and enhance the brightness of the single pixel multi-color LED device. In some embodiments, sidewalls of the reflective cups **146-1**, **148-1**, **170-1** and **172-1** as shown in FIGS. **1B-1C** may be straight, curved, wavy, multiline or the combination thereof. In some embodiments, steepness of the sidewalls of the reflective cup parts **146**, **148**, **170** and **172** may be designed to decrease the divergence of the light emitted from the light emitting region. For example, the angle of the sidewalls of the reflective cup parts **146**, **148**, **170** and **172** relative to a vertical axis perpendicular to the substrate **104** may be from at least 15 degrees to at most 75 degrees. The angle of the sidewalls of the reflective cup parts **146**, **148**, **170** and **172** relative to a vertical axis perpendicular to the substrate **104** may be from at least 5 degrees to at most 60 degrees. In some preferred embodiments, the angle of the sidewalls of the reflective cup parts **146**, **148**, **170** and **172** relative to a vertical axis perpendicular to the substrate **104** may be from at least 10 degrees to at most 50 degrees. The reflective cup can also reflect some of the light emitted from the light emitting region upwardly. For example, some of the light emitted from the light emitting region may arrive at and be reflected upward by the reflective cup parts **146**, **148**, **170** and **172**.

[0403] In some embodiments, the reflective cup may comprise metal. In some embodiments, the reflective cup may comprise dielectric material such as silicon oxide. In some embodiments, the reflective cup may comprise photosensitive dielectric material. In some embodiments, the photosensitive dielectric material may comprise SU-8, photosensitive polyimide (PSPI), or BCB.

In other embodiments, the reflective cup may comprise photoresist.

[0404] In some embodiments, the reflective cup can be fabricated by a combination of deposition, photo-lithography and etching processes. In some embodiments, the reflective cup may be fabricated by other suitable methods. In one approach, PSPI is formed into the reflective cup shape by a photolithography process. Then, a metal layer with a high reflectivity that includes one or more metals such as Pt, Rh, Al, Au, and Ag, a stacked DBR layer including TiO<sub>2</sub>/SiO<sub>2</sub> layers, or any other layer with a total reflection property including a multi-layered Omni-Directional Reflector (ODR), or a combination thereof, is deposited on the whole surface of the multi-color LED device including the reflective cup as a reflective layer by vapor deposition. Next, the reflective layer is shaded by a photoresist in the reflective cup area while the reflective layer on the other region is etched, whereby the light emitting region is exposed.

[0405] In another approach, an isolation layer including one or more of SiO<sub>2</sub>, Silicon Nitride, or SU8, which is thicker than the stacked LED structures, is deposited or spun on the stacked LED structures. Then, using a photoresist as a mask, the isolation layer is etched and formed into a reflective cup shape. Next, a metal layer with a high reflectivity that includes one or more metals such as Pt, Rh, Al, Au, and Ag, a stacked DBR layer including TiO<sub>2</sub>/SiO<sub>2</sub> layers, or any other layer with a total reflection property including a multi-layered Omni-Directional Reflector (ODR), or a combination thereof, is deposited on the whole surface of the multi-color LED device including the reflective cup as a reflective layer by vapor deposition. Finally, the reflective layer is shaded by a photoresist in the reflective cup area while the reflective layer on the other region is etched, whereby the light emitting region is exposed.

[0406] In some embodiments, as shown in FIGS. 2-6, the single pixel tri-color LED device further comprises one or more top electrodes (e.g., top electrodes **140/440**, **442** and **444**) integrated with the reflective cup. The one or more top electrodes may electrically connect with the top electrode (layer) **140/440**. For example, as shown in FIG. 4B, the electrodes **442** and **444** can be integrated with the reflective cup, e.g., the reflective cup parts **446** and **448**, respectively. Both of the top electrodes **442** and **444** may extend towards the light emitting region and electrically connect with the top electrode (layer) **140/440**. The reflective cup may perform as a common P-electrode or N-electrode for the single pixel tri-color LED device with the adoption of the one or more top electrodes. For example, when the top electrode (layer) **140/440** electrically connect with each of the LED structures (e.g. the LED structures including the light emitting layers **112/412**, **130/430** and **136/436**) and optionally the top electrodes **442** and **444**, the reflective cup may perform as a common P-electrode or N-electrode of the single pixel tri-color LED device.

[0407] In some embodiments, the reflective cup further includes one or more reflective coatings. The one or more reflective coatings may be disposed on one or more sidewalls of the reflective cup, e.g., the sidewalls of the reflective cup **146-1**, **148-1**, **170-1** and **172-1**. A bottom of each of the one or more reflective coatings does not contact the each of the LED structures, e.g. the red, green and blue LED structures. The one or more reflective coatings can reflect light emitted from the light emitting region and therefore enhance the brightness and luminous efficacy of micro-LED panels or displays. For example, the light emitted from the light emitting region may arrive at the one or more reflective coatings and may be reflected upward by the one or more reflective coatings.

[0408] The one or more reflective coatings, together with the reflective cup, can utilize reflection direction and/or reflection intensity of the light emitted from the light emitting region. For instance, the sidewalls of the reflective cup **146-1**, **148-1**, **170-1** and **172-1** be inclined at a certain angle, and therefore the one or more reflective coatings disposed on the sidewalls of the reflective cup **146-1**, **148-1**, **170-1** and **172-1** are inclined at the same angle as the sidewalls of the reflective cup **146-1**, **148-1**, **170-1** and **172-1**. When the light emitted from the light emitting region arrives at the one or more reflective coatings, the light emitted from the light emitting region would be reflected by the one or more reflective coatings in accordance with the angle of the sidewalls of the reflective cup

**146-1, 148-1, 170-1 and 172-1.**

[0409] Materials of the one or more reflective coatings may be highly reflective with a reflectivity greater than 60%, 70% or 80%, and therefore most of the light emitted from the light emitting region can be reflected. In some embodiments, the one or more reflective coatings may comprise one or more metallic conductive materials with high reflectivity. In these embodiments, the one or more metallic conductive materials may comprise one or more of aluminum, gold or silver. In other some embodiments, the one or more reflective coatings can be multi-layered. To be more specific, the one or more reflective coatings may comprise a stack of one or more reflective material layers and one or more dielectric material layers. For example, the one or more reflective coatings may comprise one reflective material layer and one dielectric material layer. In other embodiments, the one or more reflective coatings may comprise two reflective material layers and one dielectric material layer positioned between the two reflective material layers. Yet in some other embodiments, the one or more reflective coatings may comprise two dielectric material layers and one reflective material layer positioned between the two dielectric material layers. In some embodiments, the multi-layered structure may comprise two or more metal layers, which may comprise one or more of TiAu, CrAl or TiWAg.

[0410] In some embodiments, the one or more reflective coatings may be multi-layered Omni-Directional Reflector (ODR), which comprises a metal layer and a Transparent and Conductive Oxides (TCO) layer. For example, the multilayered structure may comprise a dielectric material layer, a metal layer and a TCO layer. In some embodiments, the one or more reflective coatings may comprise two or more dielectric material layers, which are disposed alternately to form a Distributed Bragg Reflector (DBR). For example, the one or more reflective coatings may comprise a dielectric material layer, a metal layer and a transparent dielectric layer. The transparent dielectric layer may comprise one or more of SiO<sub>2</sub>, Si<sub>3</sub>N<sub>4</sub>, Al<sub>2</sub>O<sub>3</sub>, or TiO<sub>2</sub>. The one or more reflective coatings may further comprise a dielectric material layer, a TCO and a DBR. In other embodiments, the one or more reflective coatings may comprise one or more metallic conductive materials with high reflection. In these embodiments, the one or more metallic conductive materials may comprise one or more of aluminum, gold or silver. In some embodiments, the reflective coatings may have the same the composition, structure and fabrication process as the reflective layers, such as **109, 115, 127, 133, and 135** above and below the light emitting layers as described above.

[0411] In some embodiments, the one or more reflective coatings can be conductive, and then the one or more reflective coatings may also perform function as electrical contacts to the single pixel multi-color LED device. For example, the top electrode (layer) **140** may be electrically connected with the one or more reflective coatings. For another example, one or more reflective coatings may be electrically connect with the one or more transparent electrode contact layers **114, 132 and 138**. The one or more reflective coatings may be patterned to not block light emitted from the light emitting region. The one or more reflective coatings may then also function as the common electrode for the LED structures within a single pixel multi-color LED device and/or the LEDs on a display panel.

[0412] In some embodiments, a top conductive layer for connecting to the electrodes is formed on the top of multi-color LED device, and the top conductive layer is electrically connected with the reflective cup. In some embodiments, the top conductive layer directly contacts with a top of the reflective cup or a bottom of the reflective cup.

[0413] In some embodiments, a bottom dielectric layer is formed between a bottom of the reflective cup and the semiconductor substrate.

[0414] In some embodiments, the one or more of reflective coatings can be produced by one or more of electron beam deposition or sputtering process.

[0415] In some embodiments, the reflective cup can have the shape of a stair like structure. FIG. **8** is a cross-sectional view of a single pixel tri-color LED device **800** with a stair-shaped reflective

cup, along the diagonal line such as **402** in FIG. 4A, in accordance with some embodiments. In some embodiments, although not all shown in FIG. 8, the single pixel tri-color LED device **800** has similar structures as any one of the single pixel tri-color LED devices shown in FIGS. 1-7 with the reflective cup parts, such as **146**, **148**, **170** and **172**, having a stair-shaped reflective cup. The stair-shaped reflective cup may be formed on the semiconductor substrate **104/404** and positioned around the light emitting region. For example, as shown in FIG. 8, from the cross-sectional view along the diagonal line such as **402** in FIG. 4A, the stair-shaped reflective cup may include two stair-shaped reflective cup parts **846** and **848**. The stair-shaped reflective cup parts **846** and **848** may be formed on the semiconductor substrate **104/404**, and positioned around the light emitting region. In some embodiments, the stair-shaped reflective cup can isolate at least some or substantially all of the light emitted from the light emitting region. For example, as shown in FIG. 8, when a height of the stair-shaped reflective cup is higher than a height of the light emitting region, the stair-shaped reflective cup parts **846** and **848** can isolate the at least some or substantially all of the light emitted from the light emitting region. Therefore, the stair-shaped reflective cup can suppress the inter-pixel light crosstalk and improve the overall contrast of LED displays.

[0416] In some embodiments, the stair-shaped reflective cup includes one or more stair structures such as **846-1**, **846-2**, **846-3**, **848-1**, **848-2**, and **848-3**. In some embodiments, the height each of the stair of the reflective cup may be the same as a height of the LED structure in the same vertical level. For example, the stair structures **846-1** and **848-1** each have the same height as the bottom LED structure. The stair structures **846-2** and **848-2** each have the same height as the middle LED structure. The stair structures **846-3** and **848-3** each have the same height as the top LED structure. Yet in some embodiments, the stair-shaped reflective cup parts **846** and **848** may have the same or different heights. The stair-shaped reflective cup can also reflect some of the light emitted from the light emitting region upwardly. For example, some of the light emitted from the light emitting region may arrive at and be reflected by the stair-shaped reflective cup parts **846** and **848** upwardly for each LED structures within the single pixel multi-color LED device in a different pattern according to the design. For example, each of the stair can adjust the focus for the light emitted (especially horizontally) in a different pattern. For example, focusing the red light more at the center and the blue light more at the edge of the light beam from the LED device. Therefore, it may reduce the divergence of the light emitted from the light emitting region, and enhance the brightness of the single pixel multi-color LED device.

[0417] In some embodiments, the stair-shaped reflective cup structure may include or form a cavity surrounding the light emitting region. The cavity may include the area surrounded by the stair-shaped reflective cup and above the semiconductor substrate **404**. The cavity may include an inner sidewall, and the inner sidewall may include a plurality of inclined surfaces. For example, as shown in FIG. 8, the stair-shaped reflective cup may include or surround the cavity, which may include the area between the stair-shaped reflective parts **846** and **848** and above the semiconductor substrate **404**. The light emitting region may be positioned in the cavity, and surrounded by the stair-shaped reflective cup parts **846** and **848**.

[0418] In some embodiments, a top of the cavity is higher than a top of the light emitting region. For example, the top of the cavity included in the stair-shaped reflective cup (e.g., the stair-shaped reflective cup parts **846** and **848**) is higher than the top of the light emitting region. In some embodiments, the cavity may include an inner sidewall, and the inner sidewall may include a plurality of inclined surfaces (e.g., inclined surfaces **846-1S**, **846-2S**, **846-3S**, **848-1S**, **848-2S**, and **848-3S**). In some embodiments, inclined angles (relative to the surface of the substrate **404**) of the plurality of inclined surfaces from bottom to top of the cavity become greater. For example, as shown in FIG. 8, the angles of the inclined surfaces **846-1S**, **846-2S**, **846-3S** are indicated as inclined angles  $\alpha$ ,  $\beta$  and  $\gamma$ , respectively. Inclined angles of the inclined surfaces **846-1S**, **846-2S**, and **846-3S** may be the same as the inclined angles of inclined surfaces **848-1S**, **848-2S**, and **848-**

3S, respectively. In some embodiments, the inclined angles  $\alpha$ ,  $\beta$  and  $\gamma$  stay the same or become greater from bottom to top of the cavity. In some preferred embodiments, the inclined angles  $\alpha$ ,  $\beta$  and  $\gamma$  may become smaller from bottom to top of the cavity, therefore the light emitted from the LED device may be more divergent toward the upper portion of the LED device. Yet in some embodiments, the inclined angles  $\alpha$ ,  $\beta$  and  $\gamma$  may be any angle according to the design. In some embodiments, the cavity may be filled with materials containing silicon, e.g., silicon oxide, and the filling can improve optical refraction, increase transparency, and/or enhance ultraviolet aging resistance and thermal aging resistance. In some embodiments, the cavity may be empty or vacuumed. In some embodiments, the inclined surfaces (e.g., inclined surfaces **846-1S**, **846-2S**, **846-3S**, **848-1S**, **848-2S**, and **848-3S**) may be straight, curved, wavy, multiline or the combination thereof.

[0419] In some embodiments, the cavity may include a plurality of sub-cavities. The sub-cavities may be formed or surrounded by respective inclined surfaces and may have different dimensions in the horizontal direction. For example, there can be three sub-cavities as shown in FIG. 8. The sub-cavity at the bottom of the cavity may include the area surrounded or restrained by the semiconductor substrate **104/404**, the inclined surfaces **846-1S** and **848-1S**, and bottom of the bonding layer **156/456**. The sub-cavity in middle of the cavity may include the area surrounded or restrained by the bottom of the bonding layer **156/456**, the inclined surfaces **846-2S** and **848-2S**, and bottom of the bonding layer **160/460**. The sub-cavity on top of the cavity may include the area surrounded or restrained by the bottom of the bonding layer **160/460**, the inclined surfaces **846-3S** and **848-3S**, and the top electrode layer **140/440** (or the opening top of the top of the stair structures **846-3** and **848-3**). In some embodiments, inclined surfaces of the sub-cavities are not arranged in a same plane. For example, as shown in FIG. 8, the sub-cavities may be formed or surrounded by the plurality of inclined surfaces **846-1S**, **846-2S**, **846-3S**, **848-1S**, **848-2S**, and **848-3S** and may have different dimensions in the horizontal direction. In some embodiments, the inclined surfaces **846-1S**, **846-2S**, and **846-3S** may not be arranged in the same plane, and the inclined surfaces **848-1S**, **848-2S**, and **848-3S** may not be arranged in a same plane. For example, the inclined surfaces **846-1S**, **846-2S**, and **846-3S** are stagger arranged in different planes in vertical direction.

[0420] In some embodiments, heights of the sub-cavities may be different. For example, a height of the sub-cavity in the middle of the cavity may be less than heights of other sub-cavities. A height of the sub-cavity at the top of the cavity may be larger than a height of the sub-cavity at the bottom of the cavity. Yet in some embodiments, each of the color LED structures is in a respectively different one of the sub-cavities. For example, the bottom red LED structure is in the sub-cavity at the bottom of the cavity and the top blue LED structure is in the sub-cavity at the top of the cavity. The middle green LED structure is in the sub-cavity in the middle of the cavity. In some embodiments, the sub-cavities may be filled with materials containing silicon, e.g., silicon oxide, and the filling can improve optical refraction, increase transparency, and/or enhance ultraviolet aging resistance and thermal aging resistance. In some embodiments, materials of the sub-cavities may be different. For example, the material of the sub-cavity at the top of the cavity may be filled with silicon oxide and the material of the sub-cavity at the bottom of the cavity may be filled with epoxy methyl silicon. In some embodiments, the sub-cavities may be empty or vacuumed.

[0421] In some embodiments, the stair-shaped reflective cup may comprise metal. In some embodiments, the stair-shaped reflective cup may comprise dielectric material such as silicon dioxide. In some embodiments, the stair-shaped reflective cup may comprise photosensitive dielectric material. In some embodiments, the photosensitive dielectric material may comprise SU-8 or photosensitive polyimide (PSPI). In other embodiments, the stair-shaped reflective cup may comprise photoresist. In some embodiments, the fabrication processes of the stair-shaped reflective cup are similarly described above with reference to the reflective cup.

[0422] In some embodiments, the single pixel multi-color LED device **800** further comprise one or more reflective coatings. The one or more reflective coatings may be disposed on one or more

inclined surfaces of the stair-shaped reflective cup, e.g., the inclined surfaces **846-1S**, **846-2S**, **846-3S**, **848-1S**, **848-2S**, and **848-3S**. A bottom of each of the one or more reflective coatings does not contact the each of the LED structures, e.g. the red, green and blue LED structures. The one or more reflective coatings can reflect light emitted from the light emitting region and therefore enhance the brightness and luminous efficacy of micro-LED panels or displays. For example, the light emitted from the light emitting region may arrive at the one or more reflective coatings and may be reflected upwardly by the one or more reflective coatings.

[0423] The one or more reflective coatings, together with the stair-shaped reflective cup, can utilize reflection direction and/or reflection intensity of the light emitted from the light emitting region. For instance, the inclined angles  $\alpha$ ,  $\beta$  and  $\gamma$  of their respectively inclined surfaces **846-1S**, **846-2S**, and **846-3S** may become smaller from bottom to top of the cavity, and therefore the one or more reflective coatings disposed on the inclined surfaces **846-1S**, **846-2S**, and **846-3S** are inclined at the same angles as the inclined surfaces **846-1S**, **846-2S**, and **846-3S**. When the light emitted from the light emitting region arrives at the one or more reflective coatings, the light emitted from the light emitting region would be reflected by the one or more reflective coatings in accordance with the inclined angles  $\alpha$ ,  $\beta$  and  $\gamma$ . The inclined angles  $\alpha$ ,  $\beta$  and  $\gamma$  may become greater, same or smaller, or the inclined angles  $\alpha$ ,  $\beta$  and  $\gamma$  otherwise are chosen according to a specific design.

[0424] Materials of the one or more reflective coatings may be highly reflective with a reflectivity greater than 60%, 70% or 80%, and therefore most of the light emitted from the light emitting region can be reflected. In some embodiments, the materials of the one or more reflective coatings are similarly described above with the reference to the reflective cup. In some embodiments, the materials of one or more reflective coatings disposed on each of inclined surfaces may be different. For example, the material of the reflective coating disposed on the inclined surface **846-1S** may be different than the materials of the reflective coatings disposed on the inclined surfaces **846-2S**, and **846-3S** respectively.

[0425] In some embodiments, the one or more of reflective coatings can be produced by one or more of electron beam deposition or sputtering process. In some embodiments, each of the one or more stair structures such as **846-1**, **846-2**, **846-3**, **848-1**, **848-2**, and **848-3** are formed layer by layer in a multi-step process. For example, the stair structures such as **846-1** and **848-1** are formed in the same step either before or after the planarized layer **454** is formed. The stair structures such as **846-2** and **848-2** are formed in the same step either before or after the planarized layer **458** is formed. The stair structures such as **846-3** and **848-3** are formed in the same step either before or after the planarized layer **462** is formed. In some embodiments, especially when layer by layer planarization is involved in the process for forming the single pixel tri-color LED device, the stair structures are formed as a result of the layer by layer process and the dislocation of the bonding of the different planarized layers including the LED structures. In some embodiments, there may be gaps (not shown in FIG. 8) between the different stair structures such as **846-1**, **846-2**, and **846-3** as a result of the layer by layer process and the dislocation of the bonding of the different planarized layers including the LED structures.

[0426] In some embodiments, the reflective cup can have a floating structure. FIG. 9 is a cross-sectional view of a single pixel tri-color LED device **900** with a floating reflective cup, along the diagonal line such as **402** in FIG. 4A, in accordance with some embodiments. In some embodiments, although not all shown in FIG. 9, the single pixel tri-color LED device **900** has similar structures as any one of the single pixel tri-color LED devices shown in FIGS. 1-8 with the floating reflective cup parts, such as **946** and **948**.

[0427] In some embodiments, the floating reflective cup may surround the light emitting region and the bottom of the reflective cup does not directly contact the semiconductor substrate **104/404**. For example, as shown in FIG. 9, the reflective cup parts **946** and **948** surround the light emitting region, and bottoms of the reflective cup parts **946** and **948** do not directly contact the semiconductor substrate **104**, e.g., there is a gap between the bottom of the reflective cup and the



substrate **104/404**. In some embodiments, the gap is filled by the planarized insulation layer **454**. In some embodiments, the light emitted from the light emitting region may arrive at and be reflected upward by the reflective cup. For example, as shown in FIG. **9**, the light emitted from the light emitting region, including light emitting from sidewalls and/or tops of the LED structures, may arrive at the reflective cup parts **946** and **948**, and be reflected upward by the reflective cup parts **946** and **948**. Therefore, it may reduce the divergence of the light emitted from the light emitting region, and enhance the brightness of the single pixel multi-color LED device.

[0428] In some embodiments, the distance between the bottom of the reflective cup and the top surface of the semiconductor substrate **104/404** can be adjusted according to the design needs. In some embodiments, the distance between the bottom of the reflective cup and the top surface of the semiconductor substrate **104/404** may be adjusted during manufacturing process of the single pixel multi-color LED device and the display panel. When manufacture of the single pixel multi-color LED device **900** is completed, the distance is fixed and not adjustable. In other embodiments, the distance between the bottom of the reflective cup and the top surface of the semiconductor substrate **104/404** may be specifically selected during the design process, and will be fixed after manufacturing the single pixel multi-color LED device **900** and the display panel. In some embodiments, the distance between the bottom of the reflective cup, such as the parts **946** and **948**, to the top surface of the substrate **404** the may be the same or smaller than the distance between the top surface of the bonding layer **408** at the bottom of the light emitting layer **412** to the top surface of the substrate **404**. In some embodiments, the distance between the bottom of the reflective cup, such as the parts **946** and **948**, to the top surface of the substrate **404** the may be larger than the distance between the top surface of the bonding layer **408** at the bottom of the light emitting layer **412** to the top surface of the substrate **404**. By adjusting the gap of the floating reflective cup, certain light from a particular portion of the single pixel multi-color LED device **900** may not be reflected or isolated, that could make the light more focused at selected portions of the device **900**.

[0429] In some embodiments, the distance between the bottom of the reflective cup and the top surface of the semiconductor substrate **404** can be less than 0.5 micrometer. In some embodiments, the distance between the bottom of the reflective cup and the top surface of the semiconductor substrate **404** can be less than 1 micrometer. In some embodiments, the distance between the bottom of the reflective cup and the top surface of the semiconductor substrate **140** can be less than 2 micrometers. In some embodiments, the distance between the bottom of the reflective cup and the top surface of the semiconductor substrate **404** can be less than 5 micrometers. In some embodiments, the distance between the bottom of the reflective cup and the top surface of the semiconductor substrate **404** can be less than 10 micrometers. In some embodiments, the distance between the bottom of the reflective cup and the top surface of the semiconductor substrate **404** can be less than 20 micrometers. In some embodiments, the distance between the bottom of the reflective cup and the top surface of the semiconductor substrate **404** can be less than 50 micrometers. In some embodiments, the distance between the bottom of the reflective cup and the top surface of the semiconductor substrate **404** can be less than 75 micrometers. In some embodiments, the distance between the bottom of the reflective cup and the top surface of the semiconductor substrate **404** can be less than 100 micrometers. Generally, the distance between bottom of the reflective cup and top surface of the semiconductor substrate **404** is decided by the height of the bottom of the light emitting layer, such as the thickness of metal bonding layer. In a preferred embodiment, the distance between bottom of the reflective cup and top surface of the semiconductor substrate **404** is not more than 20 micrometers.

[0430] In some embodiments, the reflective cup can isolate at least some of the light emitted from the light emitting region. For example, as shown in FIG. **9**, when a height of the reflective cup is higher than a height of the light emitting region, the reflective cup parts **946** and **948** can isolate the at least some of the light emitted from the light emitting region. Therefore, the reflective cup can suppress the inter-pixel light crosstalk and improve the overall contrast of LED displays. The

floating reflective cup has the same or similar composition, shape and fabrication process (except the position and location) as the reflective cups as described above.

[0431] FIGS. **1-9** only illustrate the single pixel multi-color LED devices according to some embodiments. In other embodiments, the reflective cup can be different shapes when seen from a top view or side view. That is, the sidewalls of the reflective cup surrounding the light emitting region may be circle, triangle, square, rectangular, pentagonal, hexagonal and octagonal. The sidewalls of the reflective cup may surround one light emitting region or one single pixel multi-color LED device, or a group of light emitting regions or a group of single pixel multi-color LED devices. For example, the sidewalls of the reflective cup may surround two or more light emitting regions or single pixel multi-color LED devices which are arranged in the same plane.

[0432] An array of the single pixel multi-color LED devices, each of which may comprise a reflective cup, can be utilized. Each of the reflective cup can have different shapes, when seen from a top view or plan view. For example, a reflective cup of a first single pixel multi-color LED device may be circle, and a reflective cup of an adjacent single pixel multi-color LED device may be square. In addition, the reflective cups can be electrically isolated from each other. The reflective cups can also be isolated if buffer space is provided between adjacent reflective cups or if the material of the reflective cups may not extend all the way to the boundary with the adjacent reflective cup. Alternately, a reflective coating form on the sidewall of the reflective cup can simply be extended to cover the interstitial areas between adjacent reflective cups. In another embodiment, the reflective cups can be electrically connected with each other by a common electrode such as a top electrode.

[0433] Various other modifications, changes and variations which will be apparent to those skilled in the art may be made in the arrangement, operation and details of the method and apparatus of the present invention disclosed herein without departing from the spirit and scope of the invention as defined in the appended claims. Therefore, the scope of the invention should be determined by the appended claims and their legal equivalents.

[0434] Further embodiments also include various subsets of the above embodiments including embodiments shown in FIGS. **1-9** combined or otherwise re-arranged in various other embodiments.

[0435] Various design aspects of the single pixel multi-color LED device, such as the dimensions of the layers (e.g., width, length, height, and cross-sectional area of each layer), the dimension of the electrodes, size, shape, spacing, and arrangement of the two or more LED structure layers, bonding layers, reflective layers and the conductive layers, and the configuration between the integrated circuits, pixel driver and electrical connections are selected (e.g., optimized using a cost or performance function) for obtaining the desired LED characteristics. LED characteristics that vary based on the above design aspects include, e.g., size, materials, cost, fabrication efficiency, light emission efficiency, power consumption, directivity, luminous intensity, luminous flux, color, spectrum and spatial radiation pattern.

[0436] FIG. **10A** is a circuit diagram illustrating a matrix of single pixel tri-color LED devices **1000**, in accordance with some embodiments. The circuit in FIG. **10A** includes three pixel drivers **1002**, **1004**, and **1006** and three tri-color LED devices **1008**, **1010**, and **1012**.

[0437] In some embodiments, a display panel includes a plurality of pixels, such as millions of pixels, and each pixel includes a tri-color LED device structure. In some embodiments, the LED device structures can be micro LEDs. Micro LEDs typically have a lateral dimension of 50 microns ( $\mu\text{m}$ ) or less, and can have lateral dimensions less than 10  $\mu\text{m}$  and even just a few  $\mu\text{m}$ .

[0438] In some embodiments, the pixel driver, for example **1002**, includes a number of transistors and capacitors (not shown in FIG. **10A**). The transistors include a driving transistor connected to a voltage supply, and a control transistor configured with its gate connected to a scan signal bus line. The capacitors include a storage capacitor are used to maintain the gate voltage of the driving transistor during the time that the scan signal is setting other pixels.

[0439] In this example, each of the three tri-color LED devices, for example **1008**, have its own integrated circuit (IC) pixel driver **1002**. The tri-color LED device **1008** for a single pixel can be viewed as three individual LEDs with different colors connected in parallel. For example, the red LED **1018**, green LED **1016**, and blue LED **1014**, within the same tri-color LED device **1008**, are connected to the same IC pixel driver **1002** via a shared P-electrode pad or anode.

[0440] In some embodiments, each of the red, green, and blue LEDs within the same tri-color LED device **1008** is connected to separate N-electrode pad or cathode.

[0441] In some embodiments, all the red LEDs, for example, **1018**, **1024** and **1030**, from different tri-color LED devices, are connected to the same common N-electrode **1036**. All the green LEDs for example, **1016**, **1022** and **1028**, from different tri-color LED devices, are connected to the same common N-electrode **1034**. All the blue LEDs, for example, **1014**, **1020** and **1026**, from different tri-color LED devices, are connected to the same common N-electrode **1032**. The use of the common electrodes simplifies the fabrication process and reduces the area of the LED devices especially the footprint of the electrodes.

[0442] In some embodiments, the connections for the P-electrode and N-electrode can be switched and interchanged (not shown in FIG. **10A**). For example, the red LED **1018**, green LED **1016**, and blue LED **1014**, within the same tri-color LED device **1008**, are connected to a shared N-electrode pad or cathode. Each of the red, green, and blue LEDs within the same tri-color LED device **1008** is connected to separate P-electrode pad or anode. All the red LEDs, for example, **1018**, **1024** and **1030**, from different tri-color LED devices, are connected to the same common N-electrode **1036**.

[0443] FIG. **10B** is a circuit diagram illustrating a matrix of single pixel tri-color LED devices **1000**, in accordance with some embodiments. FIG. **10B** is similar as FIG. **10A** except that in this example, each of the LED structures, in each of the three tri-color LED devices, for example **1008**, have its own integrated circuit (IC) pixel driver **1002**. For example, the red LED **1018**, green LED **1016**, and blue LED **1014**, within the same tri-color LED device **1008**, are connected to the different IC pixel drivers **1002-1**, **1002-2**, and **1002-3** respectively via a separate P-electrode pad or anode. As can be seen from FIGS. **1-9**, this type of P-electrode connections are illustrated in some embodiments.

[0444] In addition, in some embodiments as shown in FIG. **10B**, all the LEDs of different colors, from different tri-color LED devices, are connected to the same common N-electrode **1032**.

[0445] In some embodiments, the connections for the P-electrode and N-electrode can be switched and interchanged (not shown in FIG. **10B**). For example, the red LED **1018**, green LED **1016**, and blue LED **1014**, within the same tri-color LED device **1008**, are connected to the different N-electrode pad or cathode respectively. All the LEDs of different colors, from different tri-color LED devices, are connected to the same common P-electrode **1032**.

[0446] FIG. **11** is a top view of a micro LED display panel **1100**, in accordance with some embodiments. The display panel **1100** includes a data interface **1110**, a control module **1120** and a pixel region **1150**. The data interface **1110** receives data defining the image to be displayed. The source(s) and format of this data will vary depending on the application. The control module **1120** receives the incoming data and converts it to a form suitable to drive the pixels in the display panel. The control module **1120** may include digital logic and/or state machines to convert from the received format to one appropriate for the pixel region **1150**, shift registers or other types of buffers and memory to store and transfer the data, digital-to-analog converters and level shifters, and scan controllers including clocking circuitry.

[0447] The pixel region **1150** includes an array of pixels. The pixels include micro LEDs, such as a multi-color LED **1134**, integrated with pixel drivers, for example as described above. In some embodiments, an array of micro-lens (not separately shown from the LED **1134** in FIG. **11**) covers the top of the array of the multi-color LEDs. In some embodiments, an array of optical isolation structures, such as reflective structures or reflective cups (not separately shown from the LED **1134** in FIG. **11**) are formed around the array of the multi-color LEDs. In this example, the display panel

**1100** is a color RGB display panel. It includes red, green and blue pixels. Within each pixel, the tri-color LED **1134** is controlled by a pixel driver. The pixel makes contact to a supply voltage (not shown) and ground via a ground pad **1136**, and also to a control signal, according to the embodiments shown previously. Although not shown in FIG. **11**, the p-electrode of the tri-color LED **1134** and the output of the driving transistor are positioned within the LED **1134**. The LED current driving signal connection (between p-electrode of LED and output of the pixel driver), ground connection (between n-electrode and system ground), the supply voltage Vdd connection (between source of the pixel driver and system Vdd), and the control signal connection to the gate of the pixel driver are made in accordance with various embodiments.

[0448] FIG. **11** is merely a representative figure. Other designs will be apparent. For example, the colors do not have to be red, green and blue. They also do not have to be arranged in columns or stripes. As one example, apart from the arrangement of a square matrix of pixels shown in FIG. **11**, an arrangement of hexagonal matrix of pixels can also be used to form the display panel **1100**.

[0449] In some applications, a fully programmable rectangular array of pixels is not necessary. Other designs of display panels with a variety of shapes and displays may also be formed using the device structures described herein. One class of examples is specialty applications, including signage and automotive. For example, multiple pixels may be arranged in the shape of a star or a spiral to form a display panel, and different patterns on the display panel can be produced by turning on and off the LEDs. Another specialty example is automobile headlights and smart lighting, where certain pixels are grouped together to form various illumination shapes and each group of LED pixels can be turned on or off or otherwise adjusted by individual pixel drivers.

[0450] Even the lateral arrangement of devices within each pixel can vary. In FIGS. **1-9**, the LEDs and pixel drivers are arranged vertically, i.e., each LED is located on top of the corresponding pixel driver circuit. Other arrangements are possible. For example, the pixel drivers could also be located “behind”, “in front of”, or “beside” the LED.

[0451] Different types of display panels can be fabricated. For example, the resolution of a display panel can range typically from 8×8 to 3840×2160. Common display resolutions include QVGA with 320×240 resolution and an aspect ratio of 4:3, XGA with 1024×768 resolution and an aspect ratio of 4:3, D with 1280×720 resolution and an aspect ratio of 16:9, FHD with 1920×1080 resolution and an aspect ratio of 16:9, UHD with 3840×2160 resolution and an aspect ratio of 16:9, and 4K with 4096×2160 resolution. There can also be a wide variety of pixel sizes, ranging from sub-micron and below to 10 mm and above. The size of the overall display region can also vary widely, ranging from diagonals as small as tens of microns or less up to hundreds of inches or more.

[0452] Different applications will also have different requirements for optical brightness and viewing angle. Example applications include direct viewing display screens, light engines for home/office projectors and portable electronics such as smart phones, laptops, wearable electronics, AR and VR glasses, and retinal projections. The power consumption can vary from as low as a few milliwatts for retinal projectors to as high as kilowatts for large screen outdoor displays, projectors, and smart automobile headlights. In terms of frame rate, due to the fast response (nanoseconds) of inorganic LEDs, the frame rate can be as high as KHz, or even MHz for small resolutions.

[0453] Further embodiments also include various subsets of the above embodiments including the embodiments in FIGS. **1-11** combined or otherwise re-arranged in various embodiments, for example, a multi-color LED pixel device/unit with and without reflective layers, with and without planarized layers, with and without reflective cup structures including various shapes and types of positioning, with and without refractive layers, with and without micro-lenses, with and without spacers, and with different electrode connection structures.

[0454] Although the detailed description contains many specifics, these should not be construed as limiting the scope of the invention but merely as illustrating different examples and aspects of the invention. It should be appreciated that the scope of the invention includes other embodiments not

discussed in detail above. For example, the approaches described above can be applied to the integration of functional devices other than LEDs and OLEDs with control circuitry other than pixel drivers. Examples of non-LED devices include vertical cavity surface emitting lasers (VCSEL), photodetectors, micro-electro-mechanical system (MEMS), silicon photonic devices, power electronic devices, and distributed feedback lasers (DFB). Examples of other control circuitry include current drivers, voltage drivers, trans-impedance amplifiers, and logic circuits.

[0455] The preceding description of the disclosed embodiments is provided to enable any person skilled in the art to make or use the embodiments described herein and variations thereof. Various modifications to these embodiments will be readily apparent to those skilled in the art, and the generic principles defined herein may be applied to other embodiments without departing from the spirit or scope of the subject matter disclosed herein. Thus, the present disclosure is not intended to be limited to the embodiments shown herein but is to be accorded the widest scope consistent with the following claims and the principles and novel features disclosed herein.

[0456] Features of the present invention can be implemented in, using, or with the assistance of a computer program product, such as a storage medium (media) or computer readable storage medium (media) having instructions stored thereon/in which can be used to program a processing system to perform any of the features presented herein. The storage medium can include, but is not limited to, high-speed random access memory, such as DRAM, SRAM, DDR RAM or other random access solid state memory devices, and may include non-volatile memory, such as one or more magnetic disk storage devices, optical disk storage devices, flash memory devices, or other non-volatile solid state storage devices. Memory optionally includes one or more storage devices remotely located from the CPU(s). Memory or alternatively the non-volatile memory device(s) within the memory, comprises a non-transitory computer readable storage medium.

[0457] Stored on any machine readable medium (media), features of the present invention can be incorporated in software and/or firmware for controlling the hardware of a processing system, and for enabling a processing system to interact with other mechanisms utilizing the results of the present invention. Such software or firmware may include, but is not limited to, application code, device drivers, operating systems, and execution environments/containers.

[0458] It will be understood that, although the terms “first,” “second,” etc. may be used herein to describe various elements, these elements should not be limited by these terms. These terms are only used to distinguish one element from another.

[0459] The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the claims. As used in the description of the embodiments and the appended claims, the singular forms “a,” “an” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will also be understood that the term “and/or” as used herein refers to and encompasses any and all possible combinations of one or more of the associated listed items. It will be further understood that the terms “comprises” and/or “comprising,” when used in this specification, specify the presence of stated features, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

[0460] As used herein, the term “if” may be construed to mean “when” or “upon” or “in response to determining” or “in accordance with a determination” or “in response to detecting,” that a stated condition precedent is true, depending on the context. Similarly, the phrase “if it is determined [that a stated condition precedent is true]” or “if [a stated condition precedent is true]” or “when [a stated condition precedent is true]” may be construed to mean “upon determining” or “in response to determining” or “in accordance with a determination” or “upon detecting” or “in response to detecting” that the stated condition precedent is true, depending on the context.

[0461] The foregoing description, for purpose of explanation, has been described with reference to specific embodiments. However, the illustrative discussions above are not intended to be exhaustive or to limit the claims to the precise forms disclosed. Many modifications and variations

are possible in view of the above teachings. The embodiments were chosen and described in order to best explain principles of operation and practical applications, to thereby enable others skilled in the art to best utilize the invention and the various embodiments.

## Claims

1. A micro-LED pixel unit, comprising: a semiconductor substrate; a light emitting region, formed on the semiconductor substrate, including a plurality of color LED structures, a bottom of each of the plurality of color LED structures being connected to a corresponding bonding metal layer in the light emitting region, wherein each of the plurality of color LED structures includes a light emitting layer and a reflective structure at a bottom of the light emitting layer; a top electrode layer, covering each of the plurality of color LED structures and electrically contacting with each of the plurality of color LED structures, wherein the semiconductor substrate is electrically connected with each of the plurality of color LED structures; a reflective cup, surrounding the light emitting region; and a refractive structure, formed between the reflective cup and the light emitting region.
2. The micro-LED pixel unit according to claim 1, further comprising a micro-lens formed on a top surface of the refractive structure.
3. The micro-LED pixel unit according to claim 2, wherein a lateral dimension of the micro-lens is not less than a lateral dimension of the light emitting region.
4. The micro-LED pixel unit according to claim 2, wherein the reflective cup has a top opening area, and a lateral dimension of the micro-lens is less than a lateral dimension of the top opening area.
5. The micro-LED pixel unit according to claim 1, further comprising a dielectric layer formed between a bottom of the reflective cup and the semiconductor substrate.
6. The micro-LED pixel unit according to claim 1, further comprising a conductive layer formed on a top of the light emitting region, and the conductive layer is electrically connected with the reflective cup.
7. The micro-LED pixel unit according to claim 6, wherein the conductive layer directly contacts a top of the reflective cup or a bottom of the reflective cup.
8. The micro-LED pixel unit according to claim 1, wherein a top surface of the reflective cup is between a top surface of the refractive structure and the semiconductor substrate.
9. The micro-LED pixel unit according to claim 1, wherein each of the plurality of color LED structures includes a bottom conductive contact layer and a top conductive contact layer, and the light emitting layer is formed between the bottom conductive contact layer and the top conductive contact layer; and wherein the bottom conductive contact layer is electrically connected with the semiconductor substrate through the reflective structure and the corresponding bonding metal layer through a contact via, and a top surface of the top conductive contact layer of a top color LED structure contacts the top electrode layer, and an edge of the top conductive contact layer of a color LED structure under the top color LED structure contacts the top electrode layer.
10. The micro-LED pixel unit according to claim 1, wherein the semiconductor substrate is configured as an integrated circuit (IC) substrate.
11. The micro-LED pixel unit according to claim 1, wherein the reflective cup is configured as a stair-shaped reflective cup forming a cavity encompassing the light emitting region.
12. The micro-LED pixel unit according to claim 11, wherein an inner sidewall of the cavity includes a plurality of inclined surfaces.
13. The micro-LED pixel unit according to claim 12, wherein the cavity includes a bottom closest to the semiconductor substrate and a top furthest from the semiconductor substrate, and angles of the plurality of inclined surfaces relative to a surface of the semiconductor substrate decreases from the bottom to the top of the cavity.
14. The micro-LED pixel unit according to claim 12, wherein sub-cavities formed by the plurality

of inclined surfaces have different dimensions in a horizontal direction.

**15.** The micro-LED pixel unit according to claim 14, wherein inner sidewalls of the sub-cavities are not arranged in a same plane.

**16.** The micro-LED pixel unit according to claim 14, wherein heights of the sub-cavities are different.

**17.** The micro-LED pixel unit according to claim 14, wherein a height of a sub-cavity in middle of the cavity is less than heights of other sub-cavities.

**18.** The micro-LED pixel unit according to claim 14, wherein a height of a sub-cavity at a top of the cavity is larger than a height of a sub-cavity at a bottom of the cavity.

**19.** The micro-LED pixel unit according to claim 11, wherein the plurality of color LED structures includes a top color LED structure.

**20.** The micro-LED pixel unit according to claim 19, wherein a top surface of the top color LED structure is between a top surface of the cavity and the semiconductor substrate.

**21.** The micro-LED pixel unit according to claim 11, wherein the cavity includes a plurality of sub-cavities, and each of the plurality of color LED structures is positioned in a respectively different one of the sub-cavities.

**22.** The micro-LED pixel unit according to claim 1, wherein a material of the reflective cup comprises metal.

**23.** The micro-LED pixel unit according to claim 19, wherein the light emitting region includes an extended portion that is extended from one side of the light emitting layer of a color LED structure under the top color LED structure, and a contact via connects the extended portion to the top electrode layer.

**24.** The micro-LED pixel unit according to claim 1, wherein the plurality of color LED structures have a same center axis.

**25.** The micro-LED pixel unit according to claim 1, wherein the reflective structure includes a reflective layer and a thickness of the reflective layer is in a range of 5 nm to 10 nm, and a thickness of each of the plurality of color LED structures is not more than 300 nm.

**26.** The micro-LED pixel unit according to claim 1, wherein a material of the top electrode layer comprises one or more of graphene, indium tin oxide (ITO), aluminum-doped zinc oxide (AZO) or fluorine-doped tin dioxide (FTO).

**27.** The micro-LED pixel unit according to claim 1, wherein each of the plurality of color LED structures includes a respective extended portion extended from one side of the respective color LED structure, and the respective extended portion is electrically connected with the top electrode layer via a respective first contact via, and the bottom of each of the plurality of color LED structures is electrically connected with the semiconductor substrate via a respective second contact via.

---