

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250262416

Kind Code

A1

Publication Date

August 21, 2025

Inventor(s)

TAKAHASHI; Yasunao et al.

GUIDE WIRE AND METHOD FOR PRODUCING GUIDE WIRE

Abstract

A guide wire includes a core wire. The core wire includes a first wire having a proximal end and a second wire having a distal end joined to the proximal end of the first wire. The first wire is formed of a nickel titanium alloy. The second wire is formed of a cobalt chromium alloy. The core wire includes one or more projections projecting from a joint surface between the first wire and the second wire toward a distal end side of the core wire in a longitudinal cross section including the joint surface. The one or more projections are formed of an alloy containing at least one element forming the nickel titanium alloy and at least one element forming the cobalt chromium alloy.

Inventors: TAKAHASHI; Yasunao (Seto-shi, JP), KUWAHARA; Rika (Seto-shi, JP)

Applicant: ASAHI INTECC CO., LTD. (Seto-shi, JP)

Family ID: 1000008615642

Assignee: ASAHI INTECC CO., LTD. (Seto-shi, JP)

Appl. No.: 19/196871

Filed: May 02, 2025

Foreign Application Priority Data

JP 2022-187026

Nov. 24, 2022

Related U.S. Application Data

parent WO continuation PCT/JP2023/038280 20231024 PENDING child US 19196871

Publication Classification

Int. Cl.: A61M25/09 (20060101)

U.S. Cl.:

CPC **A61M25/09** (20130101); A61M2025/09083 (20130101); A61M2025/09108 (20130101); A61M2025/09133 (20130101); A61M2205/0216 (20130101); A61M2205/0233 (20130101); A61M2205/025 (20130101); A61M2205/0266 (20130101); A61M2207/00 (20130101)

Background/Summary

TECHNICAL FIELD

[0001] The technology disclosed herein relates to a guide wire and a method for producing a guide wire.

BACKGROUND

[0002] A technology of forming a core wire by joining two types of wires formed of different materials in order to increase flexibility of a distal end portion of the core wire and increase rigidity of a proximal end portion, in a guide wire to be inserted to a living body lumen such as a blood vessel has been proposed. For example, Patent Literature 1 discloses that, in a guide wire, a core wire is formed by joining a distal end side wire formed of a Ni-Ti based alloy having relatively high flexibility and a proximal end side wire formed of a Co-Cr-Ni based alloy being relatively rigid. Patent Literature 1 discloses that, since, when different metal materials are joined via thermal history in which each of the metal materials are fused, an intermetallic compound is formed in a joint part between the materials and the joint part becomes brittle, it is preferable that a thickness of a joint part between the distal end side wire and the proximal end side wire is equal to or less than 1 μm .

CITATION LIST

Patent Literature

[Patent Literature 1] JP 2017-113267 A

SUMMARY

Technical Problem

[0003] Patent Literature 1 does not sufficiently consider tensile strength of the core wire forming the guide wire, and there is a room for improvement. An object of the technology disclosed in this specification is to provide a guide wire including a core wire having excellent tensile strength while securing high flexibility in a distal end portion of the core wire and high rigidity in a proximal end portion of the core wire. A technology capable of solving the above problems is disclosed herein.

Solution to Problem

[0004] The technology disclosed herein can be implemented as follows. [0005] (1) A guide wire disclosed in this specification includes a core wire. The core wire includes a first wire having a proximal end and a second wire having a distal end joined to the proximal end of the first wire. The first wire is formed of a nickel titanium alloy. The second wire is formed of a cobalt chromium alloy. The core wire includes one or more projections projecting from a joint surface between the first wire and the second wire toward a distal end side of the core wire in a longitudinal cross section including the joining surface. The one or more projections are formed of an alloy containing at least one element forming the nickel titanium alloy and at least one element forming the cobalt chromium alloy.

Description

BRIEF DESCRIPTION OF DRAWINGS

[0006] FIG. 1 is a diagram that schematically shows the configuration of a guide wire **100** in the embodiment.

[0007] FIG. 2 is a diagram that shows the configuration of a joint part X1 between a first wire **11** and a second wire **12**.

[0008] FIG. 3 is a diagram that shows the configuration of the joint part X1 between the first wire **11** and the second wire **12**.

[0009] FIG. 4 is a flow chart that shows an example of a method for producing method of the guide wire **100**.

[0010] FIG. 5 is a diagram that shows examples and a comparative example of a core wire **10** configuring the guide wire **100**.

DETAILED DESCRIPTION OF EMBODIMENTS

A. Embodiment:

A-1. Configuration of guide wire **100**:

[0011] FIG. 1 is a diagram that schematically shows the configuration of the guide wire **100** in the embodiment. FIG. 1 shows a longitudinal cross section (YZ cross section) of the guide wire **100**. In FIG. 1, Z axis positive direction side is a distal end side (distal side) to be inserted into a body, and Z axis negative direction side is a proximal end side (near side) to be operated by a professional such as a doctor. In FIG. 1, a portion of the guide wire **100** is omitted. FIG. 1 shows a state where a center axis AX of a core wire **10** described later of the guide wire **100** is a straight line parallel to the Z axis direction, but the guide wire **100** is flexible enough to be bent. The same applies to the following figures.

[0012] In the description, regarding the guide wire **100** and the constituent members thereof, an end on the distal end side is referred to as “distal end”, the distal end and a portion in the vicinity thereof are referred to as “distal end portion”, an end on the proximal end side is referred to as “proximal end”, and the proximal end and a portion in the vicinity thereof are referred to as “proximal end portion”. The outer diameters of the guide wire **100** and the constituent members thereof each refer to a size along the direction orthogonal to the center axis AX. Longitudinal cross sections of the guide wire **100** and the constituent members thereof each refer to a cross section including the central axis AX, and transverse sections of the guide wire **100** and the constituent members thereof each refer to a cross section orthogonal to the central axis AX.

[0013] The guide wire **100** is a medical device to be inserted to the inside of a living body lumen such as a blood vessel. The guide wire **100** is used for guiding another medical device such as a catheter to a desired position in the inside of the living body lumen. The full length of the guide wire **100** ranges from about 1500 mm to 2000 mm, for example.

[0014] The guide wire **100** includes a core wire **10**, a coil body **20**, a distal end side joint part **30**, and a proximal end side joint part **40**. At least a part of the guide wire **100** may be coated with, for example, a hydrophilic resin.

[0015] The core wire **10** is a long member that extends along the center axis AX and is configured of a metal wire material. The core wire **10** includes a first wire **11** formed of a nickel titanium alloy and a second wire **12** formed of a cobalt chromium alloy. The distal end of the second wire **12** is joined to the proximal end of the first wire **11**, for example, by welding. A distance from the distal end of the core wire **10** to the joint part X1 between the first wire **11** and the second wire **12** along the center axis AX is, for example, about 50 mm to 500 mm. In the present embodiment, the joint part X1 between the first wire **11** and the second wire **12** is located at the proximal end side further than the proximal end of the coil body **20**. The configuration of the joint part X1 between the first wire **11** and the second wire **12** will be described later in detail.

[0016] The nickel titanium alloy being the forming material of the first wire **11** is an alloy containing at least Ni and Ti. The nickel titanium alloy is a flexible material as compared to the

cobalt chromium alloy being the forming material of the second wire **12**. It is preferable that the nickel titanium alloy contains 40% by mass or more and 60% by mass or less of Ni and contains 40% by mass or more and 60% by mass or less of Ti.

[0017] The cobalt chromium alloy being the forming material of the second wire **12** is an alloy containing at least Co and Cr. The cobalt chromium alloy is, for example, a Co-Ni-Cr based alloy, a Co-Cr-Ni-Mo based alloy, a Co-Cr-W-Ni based alloy, a Co-Cr-Mo based alloy, or a Co-Ni-Cr-Mo-W-Fe based alloy. It is preferable that the cobalt chromium alloy is an alloy containing at least Co, Cr, and Ni. For example, it is preferable that the cobalt chromium alloy is an alloy composed of 9 to 40% by mass of Ni, 10 to 30% by mass of Cr, and the remainder being Co, or an alloy having a composition obtained by substituting another element for part of the remainder Co in the above composition. The content of Co may be, for example, 20 to 78% by mass. When the cobalt chromium alloy contains an element other than Co, Cr, and Ni, it is preferable that the total content of the element other than Co, Cr, and Ni is equal to or less than 30% by mass. It is also preferable that the cobalt chromium alloy contains Mo as the element other than Co, Cr, and Ni, and the content of Mo is, for example, 3 to 15% by mass.

[0018] As shown in FIG. **1**, the first wire **11** includes a small diameter portion **13**, a tapered portion **14**, and a large diameter portion **15**. The small diameter portion **13** is a portion including the distal end of the core wire **10**. The large diameter portion **15** is located in a proximal end side with respect to the small diameter portion **13**. The outer diameter of the large diameter portion **15** is larger than the outer diameter of the small diameter portion **13** and ranges from about 0.1 mm to 1.0 mm, for example. The tapered portion **14** is located between the small diameter portion **13** and the large diameter portion **15**. The outer diameter of the tapered portion **14** gradually increases from the boundary position with respect to the small diameter portion **13**, toward the boundary position with respect to the large diameter portion **15**. The second wire **12** has a substantially constant outer diameter. The outer diameter of the second wire **12** is substantially equal to the outer diameter of the large diameter portion **15** of the first wire **11**. The transverse section at each position of the core wire **10** can have any shape, and is circular or rectangular, for example.

[0019] The coil body **20** is a hollow cylindrical coiled member in which one or more wire materials are spirally wound. Each wire material forming the coil body **20** may be configured of a single wire or a twisted wire formed by twisting a plurality of wires. The coil body **20** is arranged so as to surround the outer periphery of the distal end portion of the core wire **10** (specifically, the small diameter portion **13**, the tapered portion **14**, and a part of the large diameter portion **15** of the first wire **11**). The full length of the coil body **20** is about 10 mm to 500 mm, for example, and the outer diameter of the coil body **20** is about 0.2 mm to 1.2 mm, for example.

[0020] Examples of materials for forming the coil body **20** include radiolucent materials such as stainless steel (e.g., SUS302, SUS304, and SUS316), a Ni-Ti alloy and a piano wire, and radiopaque materials such as platinum, gold, tungsten or alloys thereof.

[0021] The distal end side joint part **30** (distal tip) joins the distal end of the core wire **10** and the distal end of the coil body **20**. The outer peripheral surface on the distal end side of the distal end side joint part **30** is a smooth surface (for example, approximate semi-spherical surface). The proximal end side joint part **40** joins the core wire **10** and the proximal end of the coil body **20**. Examples of materials for forming the distal end side joint part **30** and the proximal end side joint part **40** include metal solder (e.g., Au-Sn alloy, Sn-Ag alloy, Sn-Pb alloy and Pb-Ag alloy), wax materials (e.g., aluminum alloy solder, silver solder, and gold solder), and adhesives (e.g., epoxy-based adhesive).

[0022] Next, the detailed configuration of the joint part X1 between the first wire **11** and the second wire **12** of the core wire **10** will be described. FIGS. **2** and **3** are diagrams that show the configuration of the joint part X1 between the first wire **11** and the second wire **12**. FIG. **2** shows an SEM picture (1000× magnification) of a longitudinal cross section of the joint part X1 between the first wire **11** and the second wire **12**, and FIG. **3** schematically shows the configuration of the

joint part **X1**.

[0023] As shown in FIGS. **2** and **3**, the core wire **10** includes a plurality of projections **16** projecting from a joint surface **S1** between the first wire **11** and the second wire **12** toward the distal end side (side of the first wire **11**) of the core wire **10**.

[0024] The projection **16** is formed of an alloy containing at least one element forming a nickel titanium alloy being the forming material of the first wire **11** and at least one element forming a cobalt chromium alloy being the forming material of the second wire **12**. It is preferable that the alloy forming the projection **16** is an alloy containing Ni, Ti, Co, and Cr. The alloy forming the projection **16** may be an alloy in which an element forming the nickel titanium alloy is dissolved in a crystal structure of the cobalt chromium alloy, may be an alloy in which, on the contrary, an element forming the cobalt chromium alloy is dissolved in a crystal structure of the nickel titanium alloy, or may be an intermetallic compound formed of the elements forming the nickel titanium alloy and the cobalt chromium alloy. It is preferable that the content ratio of Ni in the alloy forming the projection **16** is higher than the content ratio of Ni in the cobalt chromium alloy. The composition of the alloy forming the projection **16** can be checked by composition analysis using energy dispersive X-ray spectroscopy (EDX).

[0025] It is preferable that the alloy forming the projection **16** is a material being more rigid than the nickel titanium alloy and the cobalt chromium alloy. The rigidity of each alloy is measured, for example, by measuring nano indentation rigidity under a condition of the maximum indentation load of 30 mN by using a Berkovich indenter formed of diamond by a nano indenter (iMicro) manufactured by KLA.

[0026] It is considered that, since the core wire **10** includes the projection **16** in the joint part **X1** between the first wire **11** and the second wire **12**, the projection **16** partially intrudes into the nickel titanium alloy side, so that the contact surface with the nickel titanium alloy increases and an anchoring effect occurs, and tensile strength in the joint part **X1** between the first wire **11** and the second wire **12** is improved. In view of effectively improving the tensile strength in the joint part **X1**, it is preferable that the core wire **10** includes the projection **16** having a length **L** of greater than or equal to 2 μm , it is more preferable that the core wire **10** includes the projection **16** having a length **L** of greater than or equal to 3 μm , and it is further more preferable that the core wire **10** includes the projection **16** having a length **L** of greater than or equal to 5 μm . Since the projection **16** may become a start point of breakage, it is preferable that the core wire **10** does not include the projection **16** having a length **L** exceeding 100 μm , and it is more preferable that the core wire **10** does not include the projection **16** having a length **L** exceeding 50 μm .

[0027] The length **L** of the projection **16** is a length along a direction of the center axis **AX** of the core wire **10**. The length **L** of the projection **16** is specified as below. As the joint surface **S1**, an interface is determined where, when surface analysis of a composition using EDX is performed in a longitudinal cross section of the core wire **10**, an element (for example, Ti) contained in the nickel titanium alloy is not detected for the first time when proceeding from the first wire **11** toward the proximal end side along the center axis **AX**. With respect to each projection **16**, as a boundary surface between the projection **16** and the nickel titanium alloy, an interface is determined where an element (for example, Co) contained in the cobalt chromium alloy is not detected for the first time when proceeding from the joint surface **S1** toward the distal end side along the center axis **AX**. The length from the joint surface **SI** to the boundary surface along the center axis **AX** is the length **L** of the projection **16**.

[0028] In this specification, a portion (highly gentle convex portion) having a ratio (**W/L**) of a width **W** with respect to the length **L** is equal to or greater than 3.0 in a convex portion projecting from the joint surface **S1** between the first wire **11** and the second wire **12** toward the distal end side does not correspond to the projection **16**.

[0029] FIG. **3** shows an example of types of shape of the projection **16**. In a projection **16a** shown in FIG. **3**, the contour line **18** does not include a portion extending toward the outer peripheral side

of the projection **16** as being closer to the distal end side (left side in the drawing) of the core wire **10**. On the other hand, in projections **16b**, **16c**, and **16d** shown in FIG. 3, the contour line **18** includes a portion (hereinafter, referred to as “folding back portion **18X**”) extending toward the outer peripheral side of the projection **16** as being closer to the distal end side of the core wire **10**. In order to cause a strong anchoring effect by the projection **16**, it is preferable that the core wire **10** includes the projection **16** in which the contour line **18** includes the folding back portion **18X**. [0030] It is preferable that the core wire **10** includes two or more projections **16** that are substantially not continuous from each other due to the alloy forming the projections **16**, in the longitudinal cross section. In this specification, two projections **16** being substantially not continuous from each other due to the alloy means that a thickness of a layer of the alloy existing between the two projections **16** is less than or equal to 1 μm . That is, the configuration where the two projections **16** are substantially not continuous from each other due to the thickness of a layer of the alloy existing between the projections **16** includes a form in which a layer of the alloy exists between the two projections **16** but the thickness of the layer is less than or equal to 1 μm in addition to the form in which a layer of the alloy does not exist. It is preferable that the thickness of the layer of the alloy existing between the two projections **16** is less than or equal to 0.5 μm .

A-2. Method for producing guide wire **100**:

[0031] The guide wire **100** of this embodiment can be produced by the following method, for example. FIG. 4 is a flow chart that shows an example of a production method of the guide wire **100**.

[0032] First, the first wire **11** formed of the nickel titanium alloy is prepared and roughness of an end surface of the proximal end side of the first wire **11** is controlled (**S110**). More specifically, an arithmetic mean height (S_a) of the end surface on the proximal end side of the first wire **11** is set to be greater than or equal to 0.01 μm and less than or equal to 0.5 μm . The control of the surface roughness can be implemented by, for example, polishing, blasting, plating, etching, electropolishing, thermal spraying, or the like. For example, by polishing using a polishing material, the roughness of the end surface of the first wire **11** can be controlled. At this time, polishing using a polishing material of fine granularity may be followed by polishing using a polishing material of coarse granularity. The control of roughness of the end surface of the first wire **11** may be performed simultaneously with cutting of the first wire **11**. For example, by using a cutter capable of simultaneously performing cutting and polishing of a wire, cutting of the first wire **11** and polishing of the end surface may be simultaneously performed.

[0033] Next, the core wire **10** is manufactured by joining the distal end of the second wire **12** to the proximal end of the first wire **11** (**S120**). For example, a right and left pair of clamps grip the first wire **11** and the second wire **12** such that the end surface of the proximal end side of the first wire **11** and the end surface of the distal end side of the second wire **12** face each other. At this time, positions in the first wire **11** and the second wire **12** that are distant from the respective end surfaces by a predetermined distance are gripped by the clamps. By moving the clamps in a direction in which the clamps approach to each other, the end surface of the proximal end side of the first wire **11** and the end surface of the distal end side of the second wire **12** are abutted to each other. By fixing one of the right and left pair of clamps and making the other clamp movable with respect to the fixed clamp, the end surfaces of the first wire **11** and the second wire **12** can be accurately abutted to each other. Next, the first wire **11** and the second wire **12** gripped by the clamps are electrified (heated) while being pressurized. As the electrification condition (current, time, etc.), a condition under which at least one of the end surfaces of the first wire **11** and the second wire **12** is fused is appropriately selected. The entire end surfaces of the first wire **11** and the second wire **12** may be fused or a part of the end surfaces may be fused. By electrifying the first wire **11** and the second wire **12** while pressurizing the first wire **11** and the second wire **12**, the end surfaces of both wires are softened and fused, the end surfaces of both wires push each other, so that the end surfaces are deformed so as to spread to the outer peripheral side, and the end surfaces

of both wires are joined to each other. As a result of this joining, the projection **16** described above is formed in the joint part **X1** between the first wire **11** and the second wire **12**.

[0034] Thereafter, another member is assembled to the core wire **10** (**S130**). For example, the coil body **20** is joined to the core wire **10**. The guide wire **100** of the embodiment can be produced mainly by the processes described above.

[0035] By adjusting the roughness of the end surface of the proximal end side of the first wire **11**, the length **L** of the projection **16** to be formed can be adjusted. For example, when the end surface of the first wire **11** is polished with coarse sandpaper, the length **L** of the projection **16** tends to be short, and when the end surface of the first wire **11** is polished with fine sandpaper, the length **L** of the projection **16** tends to be long.

A-3. Effect of the embodiment:

[0036] As described above, the guide wire **100** of the embodiment includes the core wire **10**. The core wire **10** includes the first wire **11** formed of a nickel titanium alloy and the second wire **12** having a distal end joined to a proximal end of the first wire **11** and being formed of a cobalt chromium alloy. The core wire **10** includes the projection **16** in the longitudinal cross section including the joint surface **S1** between the first wire **11** and the second wire **12**. The projection **16** is a portion projecting from the joint surface **S1** toward the distal end side of the core wire **10**, and is formed of an alloy containing at least one element forming a nickel titanium alloy being a forming material of the first wire **11** and at least one element forming a cobalt chromium alloy being a forming material of the second wire **12**.

[0037] It is conventionally considered that, when different metal materials are joined via thermal history in which each of the metal materials are fused, an intermetallic compound is formed in a joint part between the materials and the joint part becomes brittle and joint strength is reduced. However, the inventors of the present application have conducted intensive studies and found that, when the core wire **10** includes, in the joint part **X1** between the first wire **11** and the second wire **12**, the projection **16** formed of an alloy containing at least one element forming the nickel titanium alloy being a forming material of the first wire **11** and at least one element forming the cobalt chromium alloy being a forming material of the second wire **12**, tensile strength of the joint part **X1** is improved. It is considered that this is because the projection **16** partially intrudes into the nickel titanium alloy side, so that the contact area increases and an anchoring effect occurs. Therefore, according to the guide wire **100** of the embodiment, it is possible to provide the guide wire **100** including the core wire **10** having excellent tensile strength while securing high flexibility in a distal end portion (portion formed by the first wire **11**) of the core wire **10** and high rigidity in a proximal end portion (portion formed by the second wire **12**) of the core wire **10**.

[0038] In the guide wire **100** of the embodiment, it is preferable that the core wire **10** includes the projection **16** having a length **L** of equal to or greater than 2 μm along a direction of the center axis **AX** of the core wire **10** in the longitudinal cross section. With such a configuration, the anchoring effect by the projection **16** can be increased and tensile strength of the core wire **10** can be effectively improved.

[0039] In the guide wire **100** of the embodiment, it is preferable that the alloy forming the projection **16** contains Ni, Ti, Co, and Cr. With such a configuration, the joining property of the projection **16** and the nickel titanium alloy and the cobalt chromium alloy can be further improved and tensile strength of the core wire **10** can be further effectively improved.

[0040] In the guide wire **100** of the embodiment, it is preferable that the core wire **10** includes the projection **16** such that the projection **16** includes a folding back portion **18X** in the longitudinal cross section in which the contour line **18** of the projection **16** extends toward an outer peripheral side of the projection **16** as being closer to the distal end side of the core wire **10**. With such a configuration, the anchoring effect by the projection **16** can be further increased and tensile strength of the core wire **10** can be further effectively improved.

[0041] In the guide wire **100** of the embodiment, it is preferable that the core wire **10** includes two

or more projections **16** that are substantially not continuous from each other due to the thickness of a layer or the alloy existing between the projections **16**, in the longitudinal cross section. With such a configuration, due to the existence of the two or more projections **16**, tensile strength of the core wire **10** can be further effectively improved.

[0042] In the guide wire **100** of the embodiment, the alloy forming the projection **16** is a material being more rigid than either the nickel titanium alloy or the cobalt chromium alloy. With such a configuration, the anchoring effect by the projection **16** being relatively rigid can be increased and tensile strength of the core wire **10** can be further effectively improved.

[0043] A method of producing the guide wire **100** of the embodiment includes steps of: controlling a roughness of the end surface of the first wire **11** formed of a nickel titanium alloy such that an arithmetic mean height (S_a) is greater than or equal to $0.01\ \mu\text{m}$ and less than or equal to $0.5\ \mu\text{m}$; and producing the core wire **10** including the first wire **11** and the second wire **12** by abutting and joining the end surface of the first wire **11** and the end surface of the second wire **12**. According to the method of producing the guide wire **100** of the embodiment, the projection **16** can be formed in the joint part **X1** between the first wire **11** and the second wire **12**, and the guide wire **100** including the core wire **10** having excellent tensile strength can be produced.

EXAMPLES

[0044] FIG. 5 is a diagram that shows examples and a comparative example of the core wire **10** configuring the guide wire **100**. In producing the core wire **10** of the examples and the comparative example, as the first wire **11**, a nickel titanium alloy wire (composition (mass %): Ni: 56.1%, C: 0.032%, O: 0.025%, Ti: remainder) having a diameter of 0.42 mm was prepared, and, as the second wire **12**, a cobalt chromium alloy wire (composition (mass %): Cr: 20%, Ni: 36.5%, Mo: 10%, Mn: <0.01%, C: 0.002%, Co remainder) having a diameter of 0.42 mm was prepared. By polishing the end surface of the nickel titanium alloy wire by a polishing material having the granularity shown in FIG. 5, the nickel titanium alloy wire having the end surface of the surface roughness (arithmetic mean height S_a) shown in FIG. 5 was obtained. Thereafter, by the method described in the embodiment described above, the first wire **11** and the second wire **12** were joined to produce the core wire **10**, and tensile strength of the core wire **10** was evaluated. As the evaluation of the tensile strength of the core wire **10**, a sample was set such that the joint part was located at a center part with a chuck interval of 100 mm, and a breakage load when the sample was pulled at a speed of 10 mm/minute was measured. The core wire **10** produced under the same condition was cut in a surface passing the center axis **AX** of the core wire **10** to obtain a longitudinal cross section, the longitudinal cross section was observed by a scanning electron microscope (SEM), the presence or absence of the projection **16** in the joint part **X1** between the first wire **11** and the second wire **12** was checked, and the length **L** of the projection **16** was measured.

[0045] As shown in FIG. 5, in Examples 1 to 3 in which the projection **16** was confirmed in the joint part **X1** between the first wire **11** and the second wire **12** of the core wire **10**, the breaking load of the core wire **10** was equal to or greater than 168.4 N, which is relatively high. On the other hand, in the comparative example in which the projection **16** was not confirmed in the joint part **X1** between the first wire **11** and the second wire **12** of the core wire **10**, the breaking load was 155.3 N, which is relatively low. In Examples 1 to 3, it is considered that, the projection **16** formed in the joint part **X1** between the first wire **11** and the second wire **12** of the core wire **10** partially intruded into the nickel titanium alloy side, so that the contact surface increased and an anchoring effect occurred, and tensile strength of the core wire **10** was improved.

[0046] The disclosed embodiments have an object to improve the tensile strength of a core wire forming a guide wire.

[0047] (1) A guide wire disclosed in this specification includes a core wire. The core wire includes a first wire having a proximal end and a second wire having a distal end joined to the proximal end of the first wire. The first wire is formed of a nickel titanium alloy. The second wire is formed of a cobalt chromium alloy. The core wire includes one or more projections projecting from a joint

surface between the first wire and the second wire toward a distal end side of the core wire in a longitudinal cross section including the joining surface. The one or more projections are formed of an alloy containing at least one element forming the nickel titanium alloy and at least one element forming the cobalt chromium alloy.

[0048] It is conventionally considered that, when different metal materials are joined via thermal history in which each of the metal materials are fused, an intermetallic compound is formed in a joint part between the materials and the joint part becomes brittle and joint strength is reduced. However, the inventors of the present application have conducted intensive studies and found that, when a core wire includes, in a joint part between a first wire and a second wire, one or more projections formed of an alloy containing at least one element forming a nickel titanium alloy being a forming material of the first wire and at least one element forming a cobalt chromium alloy being a forming material of the second wire, tensile strength of the joint part is improved. It is considered that this is because the projection partially intrudes into the nickel titanium alloy side, so that the contact area increases, and an anchoring effect occurs. Therefore, with this guide wire, it is possible to provide a guide wire including a core wire having excellent tensile strength while securing high flexibility in a distal end portion (portion formed by a first wire) of the core wire and high rigidity in a proximal end portion (portion formed by a second wire) of the core wire.

[0049] (2) The guide wire described above may have a configuration in which the one or more projections each have a length of greater than or equal to 2 μm along an axial direction of the core wire in the longitudinal cross section. With this configuration, the anchoring effect by the projection can be increased and tensile strength of the core wire can be effectively improved.

[0050] (3) The guide wire described above may have a configuration in which the alloy forming the one or more projections contains Ni, Ti, Co, and Cr. With this configuration, the joining property of the projection and the nickel titanium alloy and the cobalt chromium alloy can be further improved and tensile strength of the core wire can be further effectively improved.

[0051] (4) The guide wire described above may have a configuration in which a contour line of each of the one or more projections includes a portion extending toward an outer peripheral side of the projection and toward the distal end side of the core wire in the longitudinal cross section. With this configuration, the anchoring effect by the projection can be further increased and tensile strength of the core wire can be further effectively improved.

[0052] (5) The guide wire described above may have a configuration in which at least two of the one or more projections are not substantially continuous with each other due to the thickness of a layer of the alloy existing between the at least two projections, in the longitudinal cross section. With this configuration, since the two or more projections that are substantially not continuous from each other exist, tensile strength of the core wire can be further effectively improved.

[0053] (6) The guide wire described above may have a configuration in which the alloy forming the one or more projections is a material being more rigid than either the nickel titanium alloy or the cobalt chromium alloy. With this configuration, the anchoring effect can be further increased by the projection being relatively rigid and tensile strength of the core wire can be further effectively improved.

[0054] (7) A method for producing a guide wire disclosed in this specification includes steps of: controlling a roughness of an end surface of a first wire formed of a nickel titanium alloy such that an arithmetic mean height (S_a) is greater than or equal to 0.01 μm and less than or equal to 0.5 μm ; and producing a core wire including the first wire and a second wire by abutting and joining the end surface of the first wire and an end surface of the second wire. According to this method for producing a guide wire, a projection can be formed in a joint part between the first wire and the second wire, and a guide wire including the core wire having excellent tensile strength can be produced. Note that the technology disclosed herein can be achieved in various aspects, such as guide wires, medical systems including a guide wire, and methods for producing those.

B. Modification Example

[0055] The technology disclosed herein is not limited to the above embodiments, and can be modified in various forms without departing from the gist thereof. For example, the following modification examples are also possible.

[0056] In the embodiment described above, the core wire **10** includes the first wire **11** and the second wire **12**. However, the core wire **10** may include another wire arranged in the proximal end side of the second wire **12**.

[0057] In the embodiment described above, the core wire **10** includes a plurality of the projections **16**. However, the core wire **10** may include a single projection **16**.

[0058] In the embodiment described above, the joint part **X1** between the first wire **11** and the second wire **12** of the core wire **10** is located in the proximal end side further than the proximal end of the coil body **20**. However, the joint part **X1** may be located in the distal end side further than the proximal end of the coil body **20**.

[0059] The materials for the respective members in the embodiment described above are only examples, and may be modified variously. The method for producing the guide wire **100** in the embodiment described above is only an example and can be modified variously.

REFERENCE SIGNS LIST

[0060] **10**: Core wire **11**: First wire **12**: Second wire **13**: Small diameter portion **14**: Tapered portion **15**: Large diameter portion **16**: Projection **18**: Contour **18X**: Folding back portion **20**: Coil body **30**: Distal end side joint part **40**: Proximal end side joint part **100**: Guide wire **AX**: Center axis **S1**: Joint surface **X1**: Joint part

Claims

1. A guide wire comprising: a core wire including: a first wire having a proximal end, the first wire being formed of a nickel titanium alloy; a second wire having a distal end joined to the proximal end of the first wire, the second wire being formed of a cobalt chromium alloy; and one or more projections projecting from a joint surface between the first wire and the second wire to a distal end side of the core wire in a longitudinal cross section including the joint surface, the one or more projections being formed of an alloy containing at least one element forming the nickel titanium alloy and at least one element forming the cobalt chromium alloy.
 2. The guide wire according to claim 1, wherein the one or more projections each have a length of greater than or equal to 2 μm along an axial direction of the core wire in the longitudinal cross section.
 3. The guide wire according to claim 1, wherein the alloy forming the one or more projections contains Ni, Ti, Co, and Cr.
 4. The guide wire according to claim 1, wherein a contour line of each of the one or more projections in the longitudinal cross section includes a portion extending toward an outer peripheral side of the projection and toward the distal end side of the core wire.
 5. The guide wire according to claim 1, wherein at least two of the one or more projections are not substantially continuous with one another due to the thickness of a layer of the alloy existing between the at least two projections, in the longitudinal cross section.
 6. The guide wire according to claim 1, wherein the alloy forming the one or more projections is a material that is more rigid than either of the nickel titanium alloy or the cobalt chromium alloy.
 7. A method for producing a guide wire comprising: controlling a roughness of an end surface of a first wire formed of a nickel titanium alloy such that an arithmetic mean height (S_a) is greater than or equal to 0.01 μm and less than or equal to 0.5 μm ; and producing a core wire including the first wire and a second wire by abutting and joining the end surface of the first wire and an end surface of the second wire.
-