

# US Patent & Trademark Office

## Patent Public Search | Text View

---

United States Patent	12391883
Kind Code	B1
Date of Patent	August 19, 2025
Inventor(s)	Thomas; Stephen Barry

---

### Method, process and system for recycling an asphalt-based roofing material

---

#### Abstract

The present disclosure provides a method, process and system for recycling an asphalt-based roofing material. In particular, the method, process and system are capable of removing and recovering an aggregate product, fiber product, filler product and an asphalt product from the asphalt-based roofing material. The aggregate, fiber, filler and and asphalt products each may be reused in a variety of applications.

---

<b>Inventors:</b>	<b>Thomas; Stephen Barry (Calgary, CA)</b>
<b>Applicant:</b>	<b>Northstar Clean Technologies Inc. (Delta, CA)</b>
<b>Family ID:</b>	<b>1000008240765</b>
<b>Assignee:</b>	<b>Northstar Clean Technologies, Inc. (Delta, CA)</b>
<b>Appl. No.:</b>	<b>18/917150</b>
<b>Filed:</b>	<b>October 16, 2024</b>

---

#### Publication Classification

<b>Int. Cl.:</b>	<b>C10C3/00 (20060101)</b>
<b>U.S. Cl.:</b>	
<b>CPC</b>	<b>C10C3/007 (20130101);</b>

#### Field of Classification Search

<b>CPC:</b>	<b>C10C (3/007)</b>
<b>USPC:</b>	<b>209/12.1</b>

---

## References Cited

### U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
1829544	12/1930	Schilling	210/523	D21D 5/02
4222851	12/1979	Good	208/45	C10C 3/007
4325641	12/1981	Babus et al.	N/A	N/A
4359381	12/1981	Jinno	N/A	N/A
4554055	12/1984	Rooney	N/A	N/A
4706893	12/1986	Brock	N/A	N/A
4741868	12/1987	Rooney et al.	N/A	N/A
5337965	12/1993	Chiovitti	241/DIG.38	B03B 9/065
5382449	12/1994	Hedges	427/187	E04D 1/20
5811607	12/1997	Richardt et al.	N/A	N/A
5848755	12/1997	Zickell et al.	N/A	N/A
6221260	12/2000	Chahine et al.	N/A	N/A
6743313	12/2003	Mischo	N/A	N/A
8177152	12/2011	Harmon	N/A	N/A
8789773	12/2013	Teeter, Jr	241/16	C08J 11/04
8919681	12/2013	Horton et al.	N/A	N/A
9156035	12/2014	Horton	N/A	B03B 9/065
9399713	12/2015	Ozer	N/A	N/A
9440239	12/2015	Horton	N/A	C10C 3/007
9719025	12/2016	Gordon et al.	N/A	N/A
10323149	12/2018	Russell	N/A	N/A
10669203	12/2019	Franzen et al.	N/A	N/A
10683620	12/2019	Kelley	N/A	E01C 19/05
11492455	12/2021	Charles	N/A	C08J 11/08
11976173	12/2023	Charles et al.	N/A	N/A
12180414	12/2023	Willett	N/A	C09K 8/035
2009/0229491	12/2008	Harmon	N/A	N/A
2013/0104774	12/2012	Teeter, Jr. et al.	N/A	N/A
2013/0313344	12/2012	Nykulin et al.	N/A	N/A
2014/0373749	12/2013	Zickell	241/23	E01C 19/05
2019/0255534	12/2018	Shelton, Jr. et al.	N/A	N/A
2019/0256783	12/2018	Shelton, Jr.	N/A	C10C 3/08

### FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2013204066	12/2013	AU	N/A
205295103	12/2015	CN	N/A
20050037542	12/2004	KR	N/A
100801856	12/2007	KR	N/A
2018/204904	12/2017	WO	N/A
2020/041347	12/2019	WO	N/A
2022/039965	12/2021	WO	N/A
2023/192907	12/2022	WO	N/A

### OTHER PUBLICATIONS

International Search Report issued by the Canadian Intellectual Property Office on May 16, 2023 in connection with International Patent Application No. PCT/CA2023/050230, 6 pages. cited by applicant

Written Opinion of the International Searching Authority issued by the Canadian Intellectual Property Office on May 16, 2023 in connection with International Patent Application No. PCT/CA2023/050230, 7 pages. cited by applicant

---

*Primary Examiner:* Matthews; Terrell H

*Attorney, Agent or Firm:* Patterson Intellectual Property Law, PC

---

## **Background/Summary**

### **TECHNICAL FIELD**

(1) The present disclosure generally relates to methods, processes and systems for the recycling of asphalt-based roofing materials. In particular, the present disclosure generally relates to methods, processes and systems to separate the constituents of an asphalt-based roofing shingle and recover and reuse such constituents in various applications.

### **BACKGROUND**

(2) A significant amount of unwanted material is generated from the manufacture, installation and removal of asphalt-based materials, such as roofing shingles. For example, an average residential roof removal generates 1-3 tons of roofing shingles, depending on whether the old roof consisted of 1 or 2 layers. All this adds up to an estimated total of approximately 13.5 million tons of torn-off shingles every year nationwide in North America, plus an additional 1 million tons of scrap generated by the shingle manufacturing process. This is a huge amount of unwanted material destined for already overcapacity landfills, especially since torn-off roofing shingles take at least 300 years to break down and as such some jurisdictions are increasing disposal fees, limiting disposal limits to very low percentages or banning completely. Moreover, roofing shingles cannot be composted and burning or incineration is not recommended, as it may result in the emissions of gases hazardous to human health. Since the materials in roofing shingles are similar to those materials used in hot mix asphalt cement and other road applications, unwanted roofing shingles have been identified as a material that may be diverted from landfill disposal and recycled and reused, however use in road applications is limited to very low percentages in some jurisdictions or completely banned in others.

(3) A roofing shingle is typically made up of different materials, including cellulose (paper) or a fiberglass mat, an asphalt coating and a layer of aggregate granules dispersed on the coating. The asphalt may contain a filler, which may serve to bulk out the asphalt, improve characteristics of the shingle, improve the lifespan of the shingle and/or act as a fire retardant. Developing technically viable and cost-effective recycling processes has proven to be challenging since these materials are difficult to break down/separate and therefore typically require complex process steps or equipment. For example, the asphalt and aggregate strongly adheres to one another making their separation difficult. Furthermore, the filler may be entrained within the asphalt, and therefore challenging to separate. A further problem associated with efforts to recycle these materials concerns the difficulty in shredding the shingles on a bulk basis. Because of their high granular material content, roofing shingles act like large pieces of sandpaper and as such, large piles of roofing shingles are extremely difficult to drag, flow, separate, or handle. Additionally, recycling of roofing shingles normally requires modification to standard grinding, screening, separation and

dust control equipment in order to reach the desired end use products.

(4) Some past recycling processes have used milling machines, such as rolling mills, bag mills, hammer mills, saw mills, etc. to produce a recycled roofing material which can only be used in road construction or as other similar “filler” material. Other processes have used a solvent to break down the roofing shingle, for example, U.S. Pat. No. 8,789,773 discloses a process, in which a solvent is first added to an asphalt-based material to form a mixture containing asphalt dissolved in solvent and a solids material. The solids material can be separated out by centrifugation or filtration while the asphalt dissolved in solvent can be fractionally distilled to separate the heavier asphalt phase from the lighter solvent phase. In WO 2020/041347, a process is disclosed that includes contacting a roofing shingle with a petroleum chemical in a screened tubular rotating apparatus to separate asphalt from the sand and fiberglass. U.S. Pat. App. Publ. No. 2019/0256783 also discloses a process whereby roofing shingles are placed in a dissolution vessel and a solvent stream is added to the vessel to dissolve the asphalt under agitation to yield a solids rich stream and a solvent and bitumen rich stream which can be passed through a flash drum to yield a solvent rich stream and a bitumen rich stream. Finally, U.S. Pat. No. 4,222,851 discloses a process in which roofing shingles are repeatedly washed with solvent and the solvent and asphalt are subsequently separated from one another in first and second stage evaporators.

(5) Nevertheless, there is a continuing need to provide improved methods and processes in which torn-off roofing shingles and shingle material which is the by-product of the manufacture of new roofing shingles can be recycled and reused, thus avoiding landfill.

#### SUMMARY

(6) According to an embodiment of the present disclosure, there is provided a method of separating fiber and filler from an aggregate-free asphalt-based roofing material, by: (a) passing a slurry comprising the aggregate-free asphalt-based roofing material and a solvent through a fiber separator to separate fiber from the slurry and produce an asphalt/filler/solvent mixture and a fiber product and (b) passing the asphalt/fiber/solvent mixture through a filler separator to separate filler from the asphalt/filler/solvent mixture to produce an asphalt/solvent mixture and a filler product, wherein the aggregate-free asphalt-based roofing material was derived from an asphalt-based roofing material and is substantially free of aggregate.

(7) In some embodiments, the slurry is prepared by mixing the aggregate-free asphalt-based roofing material with a solvent.

(8) In some embodiments, (a) comprises machine pressing or filter pressing the slurry in the fiber separator.

(9) In some embodiments, the fiber separator is a rotary press, a belt press, a hydraulic press, a piston press, a hydrocyclone or a screw press.

(10) In some embodiments, the aggregate-free asphalt-based roofing material was obtained by contacting an asphalt-based roofing material with at least one pressurized stream of fluid to remove substantially all aggregate from the asphalt-based roofing material and drying the asphalt-based roofing material.

(11) In some embodiments, the filler product is substantially free of fiber.

(12) In some embodiments, the filler product comprises less than 10 wt. % of the asphalt/solvent mixture.

(13) In some embodiments, (b) comprises gravity separating, machine pressing or filter pressing the asphalt/filler/solvent mixture in the filler separator.

(14) In some embodiments, the filler separator comprises a machine press, gravity separator, automated self-cleaning filter, rotary press, belt press, hydraulic press, piston press, centrifuge, self cleaning filter, automated backwash filter, cartridge filter, membrane filter or filter press.

(15) In some embodiments, the centrifuge comprises a disc centrifuge, a stacked disc centrifuge, a decanting centrifuge, a horizontal centrifuge or a filtering centrifuge.

(16) In some embodiments, the filler separator comprises a first filler separator and a second filler

separator and the first filler separator is a centrifuge and the second filler separator is a gravity separator, wherein the gravity separator receives an intermediate asphalt/solvent mixture from the centrifuge and produces the asphalt/solvent mixture and a recycle stream, which is fed to the centrifuge.

(17) In some embodiments, the gravity separator comprises a plurality of gravity separators arranged in series.

(18) In some embodiments, the filler comprises limestone.

(19) According to another embodiment, there is provided a method of separating filler from an asphalt/filler/solvent mixture, by: (a) passing the asphalt/filler/solvent mixture through a filler separator to separate the filler from the asphalt and solvent and (b) removing a filler product from the filler separator, wherein the asphalt/filler/solvent mixture was derived from an asphalt-based roofing material and is substantially free of aggregate and fiber.

(20) In some embodiments, the asphalt/filler/solvent mixture is prepared by mixing a substantially de-aggregated asphalt-based roofing material with a solvent.

(21) In some embodiments, (a) comprises gravity separating, machine pressing or filter pressing the asphalt/filler/solvent mixture in the filler separator.

(22) In some embodiments, the filler separator comprises a machine press, gravity separator, automated self-cleaning filter, rotary press, belt press, hydraulic press, piston press, centrifuge, self cleaning filter, automated backwash filter, cartridge filter, membrane filter or filter press.

(23) In some embodiments, the centrifuge comprises a disc centrifuge, a stacked disc centrifuge, a decanting centrifuge, a horizontal centrifuge or a filtering centrifuge.

(24) In some embodiments, the filler separator comprises a first filler separator and a second filler separator and the first filler separator is a centrifuge and the second filler separator is a gravity separator, wherein the gravity separator receives an intermediate asphalt/solvent mixture from the centrifuge and produces the asphalt/solvent mixture and a recycle stream, which is fed to the centrifuge.

(25) In some embodiments, the gravity separator comprises a plurality of gravity separators arranged in series.

(26) In some embodiments, the filler comprises limestone.

(27) In still another embodiment, there is provided a system for producing at least an asphalt product from an asphalt-based roofing material containing a plurality of roofing shingles, the system comprising (a) an aggregate removal unit operable to remove substantially all aggregate from the asphalt-based roofing material to produce an aggregate-free asphalt/fiber/filler mixture, (b) a fiber separation unit operable to mix the aggregate-free asphalt/fiber/filler mixture with a solvent to produce a slurry and to remove substantially all fiber from the slurry to produce an asphalt/filler/solvent mixture, (c) a filler separation unit operable to separate substantially all filler from the asphalt/filler/solvent mixture to produce an asphalt/solvent mixture and (d) a solvent separation unit operable to separate substantially all solvent from the asphalt/solvent mixture to produce an asphalt product.

(28) In some embodiments, the aggregate removal unit comprises a separation tank configured to receive and combine the asphalt-based roofing material and at least one or more pressurized streams of a first fluid and to agitate or pulse a mixture of aggregate, a second fluid and the aggregate-free asphalt/fiber/filler mixture.

(29) In some embodiments, the filler separation unit comprises a filler separator configured to receive the asphalt/filler/solvent mixture and separate filler from the asphalt/filler/solvent mixture and produce the asphalt/solvent mixture and a filler product.

(30) In some embodiments, the filler separator comprises a gravity separator, an enhanced gravity separator, a machine press or a filter press.

(31) In some embodiments, the filler separator comprises an automated self-cleaning filter, rotary press, belt press, hydraulic press, piston press, centrifuge, self cleaning filter, automated backwash

filter, cartridge filter, membrane filter or filter press.

(32) In some embodiments, the centrifuge comprises a disc centrifuge, a stacked disc centrifuge, a decanting centrifuge, a horizontal centrifuge or a filtering centrifuge.

(33) In some embodiments, the filler separator comprises a first filler separator and a second filler separator and the first filler separator is a centrifuge and the second filler separator is a gravity separator, wherein the gravity separator receives an intermediate asphalt/solvent mixture from the centrifuge and produces the asphalt/solvent mixture and a recycle stream, which is fed to the centrifuge.

(34) In some embodiments, gravity separator comprises a plurality of gravity separators arranged in series.

(35) In some embodiments, the asphalt product is substantially free of aggregate, fiber and filler.

(36) In some embodiments, there is provided an asphalt product produced according to the above-described methods.

---

## Description

### BRIEF DESCRIPTION OF THE DRAWINGS

(1) In drawings which illustrate embodiments of the invention,

(2) FIG. 1 is a schematic block diagram of a method for recycling an asphalt-based roofing material according to an embodiment of the present disclosure;

(3) FIG. 2 schematically illustrates a system for producing an asphalt product from an asphalt-based roofing material according to another embodiment of the present disclosure; and

(4) FIG. 3 schematically illustrates an embodiment of the filler separation unit of FIG. 2.

### DETAILED DESCRIPTION

(5) The following terms shall have the following meanings:

(6) The term “comprising” and derivatives thereof are not intended to exclude the presence of any additional component, step or procedure, whether or not the same is disclosed herein. In order to avoid any doubt, all compositions claimed herein through use of the term “comprising” may include any additional additive or compound, unless stated to the contrary. In contrast, the term, “consisting essentially of” if appearing herein, excludes from the scope of any succeeding recitation any other component, step or procedure, except those that are not essential to operability and the term “consisting of”, if used, excludes any component, step or procedure not specifically delineated or listed. The term “or”, unless stated otherwise, refers to the listed members individually as well as in any combination.

(7) The articles “a” and “an” are used herein to refer to one or to more than one (i.e., to at least one) of the grammatical objects of the article. By way of example, “a solvent” means one solvent or more than one solvent. The phrases “in one embodiment”, “according to one embodiment” and the like generally mean the particular feature, structure, or characteristic following the phrase is included in at least one embodiment of the present disclosure and may be included in more than one embodiment of the present disclosure. Importantly, such phrases do not necessarily refer to the same aspect. If the specification states a component or feature “may”, “can”, “could”, or “might” be included or have a characteristic, that particular component or feature is not required to be included or have the characteristic.

(8) The term “about” as used herein can allow for a degree of variability in a value or range, for example, it may be within 10%, within 5%, or within 1% of a stated value or of a stated limit of a range.

(9) Values expressed in a range format should be interpreted in a flexible manner to include not only the numerical values explicitly recited as the limits of the range, but to also include all of the individual numerical values or sub-ranges encompassed within that range as if each numerical

value and sub-range is explicitly recited. For example, a range such as from 1 to 6, should be considered to have specifically disclosed sub-ranges, such as, from 1 to 3, from 2 to 4, from 3 to 6, etc., as well as individual numbers within that range, for example, 1, 2, 3, 4, 5, and 6. This applies regardless of the breadth of the range.

(10) The terms “preferred” and “preferably” refer to embodiments that may afford certain benefits, under certain circumstances. However, other embodiments may also be preferred, under the same or other circumstances. Furthermore, the recitation of one or more preferred embodiments does not imply that other embodiments are not useful, and is not intended to exclude other embodiments from the scope of the present disclosure.

(11) The term “optional” or “optionally” means that the subsequently described event or circumstance may or may not occur, and that the description includes instances where said event or circumstance occurs and instances where it does not.

(12) The term “substantially free” refers to a composition in which a particular constituent or moiety is present in an amount that has no material effect on the overall composition. In some embodiments, “substantially free” may refer to a composition in which the particular constituent or moiety is present in the composition in an amount of less than about 10 wt. % or less than about 5 wt. %, or less than about 4 wt. %, or less than about 3 wt. % or less than about 2 wt. % or less than about 1 wt. %, or less than about 0.5 wt. %, or less than about 0.1 wt. %, or less than about 0.05 wt. %, or even less than about 0.01 wt. % based on the total weight of the composition, or that no amount of that particular constituent or moiety is present in the respective composition.

(13) The term “substantially” means a proportion of at least about 60%, or preferably at least about 70% or at least about 80%, or at least about 90%, at least about 95 wt. %, at least about 97% or at least about 99% or more, or any integer between about 70% and about 100%. For example, removing substantially all of a component from a composition may be the removal of at least about 60 wt. % or at least about 70 wt. %, etc. of the component from the composition.

(14) The term “wt. %” means weight percent.

(15) The term “integrated process” means a process where two or more related process steps of at least two separate industrial processes, which can be separately performed, are combined, so that at least one process step is common for the two processes. Moreover, in an “integrated process” as defined herein streams, fractions and/or portions produced and/or obtained in one industrial process can be used in another industrial process thereby improving the overall process efficiently more than the sum of each individual process. The integrated process reuses certain materials and streams and reduces by-products that otherwise would require treatment. In other words, the term “integrated process” means a combination of at least two unit operations which exploits the interactions between different units in order to employ resources effectively, improve energy efficiency, improve material balance, maximize profit and/or minimize costs. At least one of the two unit operations receives material and/or energy, and may be dependent on these, from the other unit operation. In an integrated process the interactions between different unit operations are considered from the outset, rather than having them optimized separately. Process integration is not limited to the design of new plants, but it also covers retrofit design, for example new units to be installed in an old plant, and the operation of existing systems.

(16) The term “asphalt-based roofing material” as used herein may refer to any new or used material that is used in connection with roofing and that contains a proportion of asphalt, such as for example, new or torn off (used) roofing shingles (which may be organic or fiberglass), new or used roofing felt or tar paper, flat roof material (which may include felt, aggregate and bitumen or asphalt sealant), unwanted material from the production of new roofing shingles or unwanted material from the installation of roofing shingles on residential or commercial buildings. In addition to asphalt, the asphalt-based roofing material may further include a proportion of aggregate fiber and filler. For example, a roofing shingle may include from about 25-45 wt. % aggregate, from about 1-10 wt. % fiber, from about 25-45% wt. % filler and from about 10-30 wt.

% asphalt, based on the total weight of the roofing shingle. For example, a roofing shingle may comprise about 35 wt. % aggregate, about 2% wt. % fiber, about 37 wt. % filler and about 20 wt. % asphalt, based on the total weight of the roofing shingle.

(17) The term “asphalt” may refer to any type of bituminous material suitable for use on a roofing material or pavement, such as asphalts, tars, pitches, bitumen or mixtures thereof. The asphalt may be either manufactured asphalt produced by refining petroleum or naturally occurring asphalt. The asphalt can be oxidized or non-oxidized. The asphalt may include any number of various additives and/or modifiers, such as inorganic fillers or mineral stabilizers, organic materials such as polymers, recycled streams, and/or ground tire rubber.

(18) The term “aggregate” may refer to solid particles having a range of sizes including fine particles to relatively coarse particles, for example sand, crushed stone, gravel, slag, or other mineral granules.

(19) The term “fiber” as used herein may refer to a solid fibrous material such as glass fiber or paper (cellulose) fiber. The term may refer to a mat of interwoven fiber strands when present in roofing shingles, or to a mixture of individual strands and/or particles of fiber.

(20) The term “filler” as used herein may refer to a material that is substantially mixed with the asphalt component of the asphalt based roofing material. In some embodiments the filler comprises a mineral material such as limestone (calcium carbonate), dolomite (calcium magnesium carbonate), or a combination thereof. In some embodiments the filler may be present as a powder or as a granular material. In some embodiments, the filler may be entrained (for example suspended) within the asphalt portion of the asphalt-based roofing material.

(21) The term “asphalt/fiber/filler slurry” as used herein may refer to a mixture of asphalt, fiber (which may include fiber particles alone or partially or completely coated with asphalt), filler and a fluid. The asphalt/fiber/filler slurry may be derived from an asphalt-based roofing material.

(22) The term “asphalt/fiber/filler mixture” as used herein may refer to a mixture of asphalt and fiber derived from an asphalt-based roofing material. The asphalt/fiber/filler mixture may include asphalt, fiber and fiber partially or completely coated with asphalt. The asphalt/fiber/filler mixture may also contain a proportion of a fluid but which proportion is less than the proportion of fluid present in the asphalt/fiber/filler slurry defined above.

(23) The term “asphalt/fiber/filler/solvent slurry” as used herein may refer to a mixture of fiber and filler carried by a mixture of asphalt and a solvent (or a blend of more than one solvent).

(24) The term “asphalt/solvent mixture” as used herein may refer to a mixture of asphalt and a solvent (or a blend of more than one solvent), where the asphalt may be fully or partially miscible with the solvent or dispersed within the solvent.

(25) The present disclosure generally relates to a method and integrative process for recycling an asphalt-based roofing material and to a system for producing an asphalt product from such an asphalt-based roofing material. It has been surprisingly found that the method, process and system of the present disclosure can break down and effectively separate the constituents of the asphalt-based roofing material (such constituents having been combined together to produce the asphalt-based roofing material) using minimal equipment and without having to input large amounts of energy. Thus, the methods, integrative process and system of the present disclosure are more economical and environmentally friendlier than state of the art methods, processes and systems. Additionally, because the constituents of the asphalt-based roofing material are effectively separated from each other in high yields and purities, they can be repurposed/used in a wide range of applications. Thus, the inventive method, integrative process and system of the present disclosure avoid the need of having to sanitarily dispose a substantial amount of unwanted material generated during the shingle manufacturing process or during the shingling or re-shingling of a roof.

(26) With reference to FIG. 1, a method **100** for recycling the asphalt-based roofing material, which according to an embodiment includes at least a plurality of roofing shingles **102**, is shown and may



generally include steps **104** to **108** and **122**. In step **104**, aggregate is removed from the asphalt-based roofing material mechanically and by density to produce an asphalt/fiber/filler mixture **112** and an aggregate product **110**. In some embodiments, the aggregate product **110** that is produced in step **104** is substantially free of asphalt, fiber and filler. In some embodiments, the method may optionally include a step of mechanically reducing the size of the asphalt-based roofing material prior to step **104**. In some embodiments, the asphalt/fiber/filler mixture **112** that is produced in step **104** is substantially free of aggregate. In step **106**, a solvent **114** is added to the asphalt/fiber/filler mixture **112** to produce an asphalt/fiber/filler/solvent slurry and the slurry is machine pressed to remove fiber from the slurry to produce an asphalt/filler/solvent mixture **124** and a fiber product **116**. In some embodiments, the asphalt/filler/solvent mixture **124** that is produced in step **106** is substantially free of fiber or aggregate or fiber and aggregate. In step **122**, the filler is separated from the asphalt/filler/solvent mixture **124** to produce an asphalt/solvent mixture **118** and a filler product **126**. In some embodiments, the asphalt/solvent mixture **118** that is produced in step **122** is substantially free of fiber or aggregate or filler or any combination thereof. In step **108**, the solvent is separated from the asphalt/solvent mixture **118** to produce an asphalt product **120**. In some embodiments, the asphalt product **120** that is produced in step **108** is substantially free of solvent, fiber, aggregate or filler or any combination thereof. In further embodiments, the solvent that is separated from the asphalt/solvent mixture in step **108** may be recovered and reused in step **106**.

(27) According to another embodiment, a system **200** operable for performing the method above to produce at least an asphalt product **218** from an asphalt-based roofing material containing a plurality of roofing shingles **202**, is generally shown in FIG. 2. The system **200** may be controlled by a controller (not shown) configured to control some or all of the operations described below. In particular, the controller may be configured to execute computer code for performing the operations described herein. In this regard, the controller may comprise a processor that may be a microprocessor or a controller for controlling the overall operation thereof. In one embodiment the processor may be particularly configured to execute program code instructions related to the functions described herein. The controller may also include a memory device. The memory device may include non-transitory and tangible memory that may be, for example, volatile and/or non-volatile memory. The memory device may be configured to store information, data, files, applications, instructions or the like. For example, the memory device could be configured to buffer input data for processing by the processor. Additionally or alternatively, the memory device may be configured to store instructions for execution by the processor.

(28) The controller may also include a user interface that allows a user to interact therewith. For example, the user interface can take a variety of forms, such as a button, keypad, dial, touch screen, audio input interface, visual/image capture input interface, input in the form of sensor data, etc. Still further, the user interface may be configured to output information to the user through a display, speaker, or other output device. A communication interface may provide for transmitting and receiving data through, for example, a wired or wireless network such as a local area network (LAN), a metropolitan area network (MAN), and/or a wide area network (WAN), for example, the Internet. The communication interface may enable the controller to communicate with one or more further computing devices, either directly, or via a network. In this regard, the communication interface may include one or more interface mechanisms for enabling communication with other devices and/or networks. The communication interface may accordingly include one or more interface mechanisms, such as an antenna (or multiple antennas) and supporting hardware and/or software for enabling communications via wireless communication technology (e.g., a cellular technology, communication technology, Wi-Fi and/or other IEEE 802.11 technology, Bluetooth, Zigbee, wireless USB, NFC, RF-ID, WiMAX and/or other IEEE 802.16 technology, and/or other wireless communication technology) and/or a communication modem or other hardware/software for supporting communication via cable, digital subscriber line (DSL), USB, FireWire, Ethernet, one or more optical transmission technologies, and/or other wireline networking methods. Further,

the controller may include various modules which may be configured to, in conjunction with the processor, direct operations for removing the aggregate from the roofing shingles in the aggregate removal unit, separating the fiber in the fiber separator unit, separating filler in the filler removal unit and/or separating the solvent in the solvent separator unit to ultimately produce the asphalt product as described herein.

(29) As illustrated, the system **200** may include an aggregate removal unit **204**. The aggregate removal unit **204** is operable to perform step **104** above and may include a separation tank **222** configured to receive and combine the roofing shingles **202** and at least one or more pressurized streams of fluid **224**. The separation tank **222** may also be configured to agitate or pulse a mixture of a fluid (which may be the same fluid as the pressurized stream of fluid or a different fluid), the roofing shingles and aggregate that may be contained therein. The aggregate removal unit **204** may further include a dewatering and/or drying apparatus **228** configured to receive the mixture contained in the separation tank **222** and to remove moisture from the mixture. Thus, as will be described in more detail below, the separation tank **222** is configured to receive and combine the roofing shingles **202** and one or more pressurized streams of fluid **224** and to agitate or pulse the mixture of fluid, roofing shingles and aggregate to produce an asphalt/fiber/filler slurry **226** and an aggregate product **210**. The dewatering and drying apparatus **228** is configured to receive the asphalt/fiber/filler slurry **226** and remove moisture from the asphalt/fiber/filler slurry **226** to produce an asphalt/fiber/filler mixture **212**. In some embodiments, the moisture that is removed in the dewatering and drying apparatus **228** may be recovered and reused in system **200**.

(30) The system **200** may also include a fiber separation unit **206**. The fiber separation unit **206** is operable to perform step **106** above and may include a mixing tank **232** configured to receive and combine the moisture-removed mixture from the aggregate removal unit **204** and a liquid. The fiber separation unit **206** may further include a fiber separator **236** configured to receive the contents in the mixing tank **232** and separate solids from liquids. Thus, as will be described in more detail below, the mixing tank **232** is configured to receive and combine the asphalt/fiber/filler mixture **212** and a solvent **230** to produce an asphalt/fiber/filler/solvent slurry **234**. The fiber separator **236** is configured to receive the asphalt/fiber/filler/solvent slurry **234** and separate fiber from the asphalt/fiber/filler/solvent slurry **234** to produce an asphalt/filler/solvent mixture **242** and a fiber product **214**.

(31) The system **200** may also include a filler separation unit **240**. The filler separation unit **240** is operable to perform step **122** described above and may include a first filler separator **244** configured to receive asphalt/filler/solvent mixture **242** and produce an asphalt/solvent mixture **216** and a filler product **246**.

(32) In some embodiments, filler separator **244** may alternatively or additionally produce an intermediate asphalt/solvent mixture **248** which is received in a second filler separator **250**. Second filler separator **250** is configured to produce a recycle stream **252** which is received by first filler separator **244** and asphalt/solvent mixture **216**.

(33) System **200** removes fiber and filler from the roofing shingles **202** as separate fiber product **214** and filler product **246**. This may be advantageous as if fiber and filler were separated from asphalt/fiber/filler mixture **212**, separation of a mixture of filler and fiber may be operationally challenging to achieve. Finally, the system **200** may include a solvent separation unit **208**. The solvent separation unit **208** may be used to perform step **108** above and may include a solvent separator **238** configured to receive a mixture of liquids and heat the mixture to separate the liquids in the mixture. Thus, as will be described in more detail below, the solvent separator **238** is configured to receive the asphalt/solvent mixture **216** and heat the mixture to separate the solvent from the mixture to produce an asphalt product **218**. In some embodiments, the solvent separation unit may further include a condenser configured to condense and recover the solvent separated from the mixture so that it can be reused in the system **200**.

(34) In a further embodiment, the system **200** may optionally include a pretreatment unit (not

shown). The pretreatment unit may include a grinder that is operable to crush or grind the asphalt-based roofing material as needed based on production and availability in order to reduce the roofing material to a desired particle size (for e.g., to a maximum of less than about 1 inch). In one embodiment, the particle size is screened to  $\frac{3}{4}$  inch minus (i.e.,  $\frac{3}{4}$  of an inch or less). It should be noted that the particles are generally irregularly shaped. In some embodiments, the asphalt-based roofing material may first be cleaned of nails and other debris by hand or by using a magnet before being sent to the grinder. In other embodiments, nails and debris may be removed after the feed hopper or after first stage of separation. The pretreatment unit may further include a feed system configured to receive the asphalt-based roofing material from the grinder and which may be interlocked with other plant components and controlled by the controller. The feed system may include a feed hopper which may be equipped with a drive motor, a strainer (e.g., comprising one or more screens), and one or more conveyors (e.g., comprising an auger). The feed system may be calibrated to regulate flow of the asphalt-based roofing material to the aggregate removal unit **204** as controlled by the controller.

(35) Removal of Aggregate (Step **104**) in the Aggregate Removal Unit (**204**)

(36) As described above, in step **104** aggregate is removed from the roofing shingles **102** to produce the aggregate product **110** and the asphalt/fiber/filler mixture **112**. In the embodiment shown in FIG. **2**, this removal may be accomplished in the aggregate removal unit **204** mechanically and by density by physically contacting the roofing shingles **202** with one or more pressurized streams of fluid **224** in the separation tank **222** to separate aggregate from the roofing shingles and by agitating or pulsing the mixture of fluid, roofing shingles and separated aggregate contained within the separation tank **222**. In other embodiments the roofing shingles may be physically contacted with the one or more pressurized streams of fluid **224** prior to the separation tank **222**.

(37) The separation tank **222** may be shaped, sized and configured to hold any suitable volume of fluid and is also operable to agitate or pulse the fluid contained therein and therefore may include an inner cavity and a mixing device. Examples of mixing devices include, but are not limited to, vanes, paddles, blades, screw elements, or other elements of dynamic mixers such as rotating or co-rotating screw mixers, planetary and double planetary mixers, impellers, and the like or baffle elements within a static mixer, such as plates, helices, vanes, paddles, or blades, intended to disrupt laminar flow and cause mixing within the static mixer. In an embodiment, the mixing device is a movable paddle or block that creates an up and down or side to side movement within separation tank **222** to pulse the fluid in the separation tank **222**. The separation tank **222** may be in fluid communication with one or more sources of fluids (such as a holding or buffer tank) via one or more conduits which supply the one or more pressurized streams (or jets) of fluid **224** to the separation tank **222**. Each stream of fluid **224** supplied to and received by the separation tank **222** may be the same fluid or a different fluid.

(38) The roofing shingles **202** may be introduced into some, or all, of the one or more pressurized streams of fluid **224** supplied to the separation tank **222** by any suitable method. For example, the roofing shingles **202** may be supplied to a funnel or hopper as described above that is in communication with some, or all, of the one or more streams of fluid **224**. The controller may control the amount of the roofing shingles **202** which are contacted by a stream of fluid **224**. Contact between the roofing shingles **202** and the streams of fluid **224** may be of sufficient force to dislodge aggregate from the roofing shingles **202** such that aggregate is separated from the roofing shingles **202**. In addition, the force may be sufficient to dislodge asphalt that is adhered to and coating the aggregate such that aggregate that is separated is substantially free of adhered asphalt.

(39) The elevated flow rate and/or pressure of the one or more streams of fluid **224** entering the separation tank **222** may be sufficient to cause cavitation of the fluid within separation tank **222**. As is well known, cavitation is a phenomenon in which the local static pressure of a fluid is reduced to below the vapor pressure of the fluid causing the formation of small vapor filled cavities (or

bubbles) within the fluid. Thus, one or more fluid conduits that supply the streams of fluid **224** to separation tank **222** may be configured to produce Venturi effects via a relatively narrow or constricted section within the conduit followed by a wider section that is positioned close to the outlet. As the stream of fluid **224** passes through the constricted section, the pressure of the fluid will decrease as the flow rate increases. The combination of pressure and kinetic energy can create a cavitation cavern downstream of the constriction generating high energy cavitation bubbles. These cavitation bubbles may subsequently collapse, generating shockwaves waves within the fluid. As these shockwaves contact roofing shingles **202** within separation tank **222**, a cavitation force is applied to roofing shingles **202** sufficient to separate aggregate from the other constituents of the roofing shingles **202**. The cavitation force may also be sufficient to dislodge asphalt adhered to and/or coating the aggregate particles such that the aggregate is substantially free of asphalt.

(40) Further, each of the one or more fluid conduits may be positioned such that the outlet of each of the one or more conduits is generally directed towards the outlet of another of the one or more conduits. This means that one stream of fluid **224** exiting from one conduit will collide with another stream of fluid **224** exiting from another conduit within separation tank **222**. This may further increase the turbulent flow of fluid **224** within separation tank **222** and may also increase contact between roofing shingles **202** and stream of fluid **224** to assist in separating aggregate from the roofing shingles **202**.

(41) In one embodiment, the separation tank **222** may have one pair of conduits, where the outlet of the first conduit may be generally directed towards the outlet of the second conduit such that the stream of fluid **224** exiting through the outlet of the first conduit will collide with the stream of fluid **224** exiting through the outlet of the second conduit.

(42) In other embodiments, the separation tank **222** may have more than one pair of conduits where the outlet of the first conduit in each pair may be generally directed towards the outlet of the second conduit in each pair. For example, the separation tank **222** may have 2, 4, 6, 8, 10, 12 or more pairs of conduits where the outlet of the first conduit in each pair may be generally directed towards the outlet of the second conduit in each pair. Each of the pairs of conduits may be positioned at different locations in separation tank **222**, for example each pair of conduits may be vertically spaced from the next pair of conduits.

(43) In still other embodiments, in each of the pairs of conduits described above, the outlet of the first conduit may directly oppose the outlet of the second conduit in each pair. This may increase the contact between the opposing streams of fluid, increasing the number and the force of collisions between the roofing shingles **202** and streams of fluid **224**.

(44) In a further embodiment, the separation tank **222** may include more than two conduits with outlets generally directed towards each other. For example, the separation tank **222** may have three conduits, where the outlets of the first, second and third conduits are directed towards each other. In other embodiments, separation tank **222** may have 4, 5 or 6 or more conduits all having outlets directed towards each other.

(45) In another embodiment, the separation tank **222** may have a single conduit, where the outlet of the single conduit is generally directed towards an impact surface such as a contact plate, or the inner surface of separation tank **222**. The use of an impact surface other than the inner surface of separation tank **222** may be preferable to reduce wear of the inner surface of separation tank **222** caused by impact of the stream of fluid **224**. The force of the stream of fluid impacting the contact plate may be of sufficient force to dislodge aggregate from the roofing shingles **202** and/or cause cavitation of the fluid within separation tank **222** as described above.

(46) In further embodiments, the separation tank **222** may have multiple sets of single conduits where the outlets of the single conduits are generally directed towards an impact surface. For example, the separation tank **222** may have 2, 3, 4, 5, 6, 7, 8 or more sets of single conduits where the outlets of the single conduits are generally directed towards an impact surface.

(47) In still other embodiments, for each impact surface in the separation tank **222** there may be

more than one conduit where the outlet of each conduit is generally directed towards the impact surface. For example, each impact surface may have 2, 3, 4, 5, 6 or more conduits where the outlet of each conduit is generally directed towards the impact surface.

(48) The separation tank **222** is further configured to agitate or pulse a mixture of fluid, aggregate and roofing shingles contained therein. Agitation may be achieved by any known mixing device as described above, such as for example, by rotation of a paddle or impeller configured to circulate the roofing shingles that have fallen towards the lower region of the separation tank **222** (and into the fluid contained therein) in the mixture in a generally upwards direction. By increasing the contact time of the roofing shingles **202** and fluid via agitation or pulsing, separation of aggregate from the roofing shingles **202** may be further increased in separation tank **222**.

(49) In one embodiment, the pressure of the one or more pressurized streams of fluid **224** supplied to and received by the separation tank **222** may range between about 100 psi to about 150 psi, or about 105 psi to about 145 psi, or about 110 psi to about 140 psi, or about 115 psi to about 135 psi, or about 120 psi to about 130 psi. In an embodiment, the flow rate of the one or more pressurized streams of fluid **224** supplied to and received by the separation tank **222** may range between about 50 m.sup.3/hr to about 100 m.sup.3/hr, or about 55 m.sup.3/hr to about 95 m.sup.3/hr, or about 60 m.sup.3/hr to about 90 m.sup.3/hr, or about 65 m.sup.3/hr to about 85 m.sup.3/hr, or about 70 m.sup.3/hr to about 80 m.sup.3/hr.

(50) In another embodiment, the separation tank **222** may be generally cylindrical and orientated vertically. In a specific embodiment, the separation tank **222** may have an internal volume of about 10 m.sup.3 to about 100 m.sup.3, or about 20 m.sup.3 to about 90 m.sup.3, or about 30 m.sup.3 to about 70 m.sup.3, or about 40 m.sup.3 to about 60 m.sup.3.

(51) In another embodiment, the separation tank **222** may be generally rectangular and orientated horizontally. In a specific embodiment, the separation tank **222** may have an internal volume of about 1 m.sup.3 to about 10 m.sup.3, or about 2 m.sup.3 to about 9 m.sup.3, or about 3 m.sup.3 to about 7 m.sup.3, or about 4 m.sup.3 to about 6 m.sup.3 or about 5 m.sup.3.

(52) The fluid supplied to and received by the separation tank **222** as described above may be selected from a fluid or blend of fluids having a lower specific gravity than the specific gravity of aggregate, such that, once the aggregate has been separated from roofing shingles **202**, it will migrate towards the lower end or bottom of separation tank **222**. An aggregate product **210** may then be removed from such lower end or bottom of the separation tank **222** and further processed or repurposed as will be further described below. The fluid or blend of fluids may also have a specific gravity that is greater than the specific gravity of the remaining constituents of roofing shingles **202**, namely a mixture of asphalt, fiber and filler (wherein the filler may be still entrained within the asphalt), so that this mixture will migrate to the upper end of separation tank **222** for removal as an asphalt/fiber/filler slurry **226**. Separation tank **222** may be, for example, rectangular and shaped such that roofing shingles **202** and fluid in the one or more streams of fluid **224** entering the separation tank **222** may enter at a first end, and are allowed to partially settle as the mixture travels from the first end to a second end (which may be at an opposite end of separation tank **222** to the first end), where asphalt/fiber/filler slurry **226** is removed. As will be appreciated, as the mixture moves from the first end to the second end of separation tank **222**, the turbulence of the mixture within separation tank **222** will decrease. Lighter material, such as entrained plastics from roofing shingles **202** will float to the surface of the mixture within separation tank **222** and may exit separation tank **222** by an overflow weir.

(53) Furthermore, in some embodiments, the fluid or blend of fluids described above may also be immiscible with asphalt so that the asphalt present in the roofing shingles **202** is not lost through dissolution into the fluid or blend of fluids. For example, in one embodiment such fluid may include a glycol, such as ethylene glycol and propylene glycol. In another embodiment, the fluid may include an alcohol, such as a straight or branched chain C.sub.1-C.sub.10 alcohol or mixture thereof. In another embodiment the C.sub.1-C.sub.10 alcohol is ethanol, n-propanol, isopropanol

(IPA), n-butanol, propanol, or t-butanol. In yet another embodiment the fluid may comprise dimethylformamide (DMF), acetonitrile, acetone, tetrahydrofuran dimethylsulfoxide (DMSO), methylethylketone (MEK), or an aromatic solvent such as benzene, methylbenzene (toluene), dimethylbenzene or ethylbenzene.

(54) In one specific embodiment, the fluid supplied to and received by the separation tank **222** via the one or more conduits comprises water. A pressurized stream of water may enter the separation tank **222** through the one or more conduits at a pressure ranging between about 100 psi to about 150 psi or about 105 psi to about 145 psi, or about 110 psi to about 140 psi, or about 115 psi to about 135 psi, or about 120 psi to about 130 psi. In an embodiment, the flow rate of the stream of water may range between about 50 m.sup.3/hr to about 130 m.sup.3/hr, or about 55 m.sup.3/hr to about 125 m.sup.3/hr, or about 60 m.sup.3/hr to about 120 m.sup.3/hr, or about 65 m.sup.3/hr to about 115 m.sup.3/hr, or about 70 m.sup.3/hr to about 110 m.sup.3/hr or about 75 m.sup.3/hr to about 105 m.sup.3/hr or about 80 m.sup.3/hr to about 100 m.sup.3/hr or about 85 m.sup.3/hr to about 95 m.sup.3/hr. The pressure and flow rate may be selected so they are sufficient to cause cavitation in the separation tank **222**.

(55) In an embodiment, the fluid contained within the separation tank **222** and/or the one or more streams of fluid **224** contacting the roofing shingles **202** are at ambient temperature. Aside from the lower energy input required, performing step **104** at ambient temperatures may advantageously assist in the separation of aggregate from the roofing shingles **202** since at lower temperatures, the roofing shingles **202** tend to be more brittle (and less ductile) allowing the aggregate to separate from the roofing shingles **202** more easily.

(56) In a further embodiment, the fluid contained in the separation tank **222** and/or the one or more streams of fluid **224** contacting the roofing shingles **202** may be at an elevated temperature, i.e. a temperature that is greater than ambient temperature. The elevated temperature may be attained by any suitable method known in the art. For example, the separation tank **222** and or one or more conduits may include heating coils or heat traces. Alternatively, the streams of fluid **224** supplied to the separation tank **122** through the one or more conduits may be preheated to an elevated temperature relative to the fluid contained in separation tank **222**.

(57) As described above, aggregate separated from the roofing shingles **202** may migrate towards the lower end or bottom of the separation tank **222** during agitation. The lower end of the separation tank **222** may have a tapered frustoconical shape such that separated aggregate is channeled towards the lower end of the separation tank **222** and recovered from the separation tank **222** as an aggregate product **210**. The aggregate product **210** that is recovered may be dewatered and/or dried using any suitable means known to those skilled in the art, such as by passing the aggregate product **210** over a vibrating screen/shaker deck or by air drying. In some embodiments, moisture that is removed during drying may be collected, filtered or desilted in one or more purification steps and then recycled back to the separation tank **222**.

(58) The separation of aggregate from the roofing shingles **202** during step **104** may be highly efficient such that substantially all of the aggregate originally present in the roofing shingles **202** is recovered from separation tank **222** as the aggregate product **210** and therefore the roofing shingles **202** remaining in separation tank **222** are substantially free of aggregate, i.e., aggregate-free asphalt-based roofing shingles. According to one embodiment, at least about 90 wt. % of the total weight of aggregate originally present in the roofing shingles **202** is recovered as aggregate product **210**. In other embodiments at least about 91 wt. %, or at least about 92 wt. %, or at least about 93 wt. %, or at least about 94 wt. %, or at least about 95 wt. %, or at least about 96 wt. %, or at least about 97 wt. %, or at least about 98 wt. %, or at least about 99 wt. % of the total weight of aggregate originally present in roofing shingles **202** is recovered as aggregate product **210**.

(59) As described above, the asphalt/fiber/filler slurry **226** may be removed from the upper end of the separation tank **222**. The upper end of the separation tank **222** may have a tapered frustoconical shape such that the asphalt/fiber/filler slurry **226** is channeled towards the central upper end of the

separation tank **222** for easier removal.

(60) The recovery of asphalt and fiber in the asphalt/fiber/filler slurry **226** from the separation tank **222** may be highly efficient such that the wt. ratio of asphalt to fiber to filler in the asphalt/fiber/filler slurry **226** is similar to the wt. ratio in the roofing shingles **202**, i.e., about a 20:2:37 wt. ratio of asphalt to fiber to filler. The asphalt/fiber/filler slurry **226** also includes a proportion of fluid. According to an embodiment in which the fluid is water, the asphalt/fiber/filler slurry **226** can contain at least about 80 wt. % water, based on the total weight of the asphalt/fiber/filler slurry for example, at least about 81 wt. % water, at least about 82 wt. % water, at least about 83 wt. % water, at least about 84 wt. % water, at least about 85 wt. % water, at least about 86 wt. % water, at least about 87 wt. % water, at least about 88 wt. % water, at least about 89 wt. % water, at least about 90 wt. % water, at least about 91 wt. % water, at least about 92 wt. % water, at least about 93 wt. % water, at least about 94 wt. % water, at least about 95 wt. % water, based on the total weight of the asphalt/fiber/filler slurry.

(61) In another embodiment not shown in FIG. **2**, the removal of aggregate from roofing shingles **202** and the separation of aggregate and asphalt/fiber/filler slurry **226** may occur in separate locations. For example, roofing shingles **202** may first enter a first tank where contact with one or more streams of fluid **224** occurs in order to separate aggregate in a similar manner as described above. In this embodiment, separation of aggregate from asphalt/fiber/filler slurry **226** does not occur in the same tank where cavitation occurs. Instead, a mixture of aggregate, asphalt/fiber/filler slurry **226** and fluid may feed into a separation apparatus in fluid communication with the first tank, where separation of aggregate product **210** from asphalt/fiber/filler slurry **226** occurs. The separation apparatus may be any suitable apparatus operable to separate aggregate from asphalt/fiber/filler slurry **226** such as a separation tank, a vertical or horizontal classification tank or a jig concentrator.

(62) In an embodiment, the separation apparatus may be a jig such as a water or an air pulsed jig. A water jig may include an inclined jig bed (such as a screen or sieve) within a tank of fluid, such as fluid **224**. A stream of aggregate and asphalt/fiber/filler slurry **226** may be fed on top of the jig bed at the higher end of the inclined jig bed. The fluid within the tank may be pulsed such that a column of fluid rises up through the jig bed, suspending the particles (e.g. the aggregate and asphalt/fiber/filler particles) within the column of fluid. When the fluid level drops back down, the particles will be redeposited onto the jig bed. As the pulsing of the fluid is repeated, those particles with a higher specific gravity (i.e., aggregate) will redeposit faster than those particles with a lower specific gravity (i.e., asphalt/fiber). As such, the aggregate and asphalt/fiber will be separated by density and can be extracted from lower end of jig bed separately.

(63) Referring to FIG. **2** the asphalt/fiber/filler slurry **226** that is recovered from the separation tank **222** is sent to and received by a dewatering or drying apparatus **228** where fluid is removed from the asphalt/fiber/filler slurry **226** to produce the asphalt/fiber/filler mixture **212**. Such removal can not only increase process efficiency but can also reduce sludge and/or emulsion formation from possibly occurring in subsequent steps **106** and **108** of method **100**.

(64) The dewatering or drying apparatus **228** may be any suitable type of dryer equipment operable for removing a proportion of fluid from the asphalt/fiber/filler slurry **226**. For example, the drying apparatus **228** may be a vacuum dryer, tray dryer, fluidized bed dryer, rotary dryer, dewatering screen or spray dryer. In another embodiment, the drying apparatus **228** is a centrifuge, for example a decanter centrifuge. The use of a decanter centrifuge may be preferred since it is able to operate at a high throughput while at ambient temperature. In another embodiment, the drying apparatus **228** may be a hydrocyclone. The asphalt/fiber/filler slurry **226** may first enter the hydrocyclone where a first proportion of the fluid from the asphalt/fiber/filler slurry **226** is removed, for example from about 70-95 wt. % of the total weight of fluid present in asphalt/fiber/filler slurry **226** is removed. The drying apparatus **228** may further include a secondary drying apparatus, such as a fluidized bed dryer located downstream of the hydrocyclone, where a second proportion of fluid is removed from

the asphalt/fiber/filler slurry.

(65) In some embodiments, the fluid that is removed from the asphalt/fiber/filler slurry **226** by the drying apparatus **228** may be recovered and recycled back to the separation tank **222**. When the fluid that is removed is water, such water may be treated to remove impurities before being recycled back to the separation tank **222**. For example, suspended solids in the water may be removed using a de-silter prior to being recycled back to the separation tank **222**.

(66) The dewatering or drying apparatus **228** may be configured and operable to remove only fluid from the asphalt/fiber/filler slurry **226** and thus, substantially all of the asphalt, fiber and filler in the asphalt/fiber/filler slurry **226** may be recovered as asphalt, fiber and filler in the asphalt/fiber/filler mixture **212**. In an embodiment, more than 80 wt. % of the total weight of asphalt, fiber and filler in the asphalt/fibre/filler slurry **226** is recovered as asphalt, fiber and filler in the asphalt/fiber/filler mixture **212**, or more than 85% wt. %, or more than 90% wt. %, or more than 95% wt. %, or more than 98% wt. % of the total weight of asphalt, fiber and filler in asphalt/fibre/filler slurry **226** is recovered as asphalt, fiber and filler in the asphalt/fiber/filler mixture **212**.

(67) Generally speaking, the asphalt/fiber/filler mixture **212** will have a fluid content that is less than the fluid content of the asphalt/fiber/filler slurry **226**. According to one embodiment, when the fluid is water, the asphalt/fiber/filler mixture **212** can contain less than about 1 wt. % water, based on the total weight of the asphalt/fiber/filler mixture, for example, less than about 2 wt. % water, or less than about 4 wt. % water, or less than about 6 wt. % water, or less than about 8 wt. % water, or less than about 10 wt. % water, or less than about 12 wt. % water, or less than about 14 wt. % water, or less than about 15 wt. % water, based on the total weight of the asphalt/fiber/filler mixture.

(68) As described above, substantially all of the aggregate may be separated from the roofing shingles **202**, such that the asphalt/fiber/filler mixture **212** is substantially free of aggregate. In one embodiment, the asphalt/fiber/filler mixture **212** may contain less than about 5 wt. % of aggregate, based on the total weight of the asphalt/fiber/filler mixture. In other embodiments, the asphalt/fiber/filler mixture may contain less than about 4 wt. %, or less than about 3 wt. %, or less than about 2 wt. %, or less than about 1 wt. %, based on the total weight of the asphalt/fiber/filler mixture. Accordingly, the aggregate removal unit **204** may be operable to remove at least 95 wt. % of the total weight of aggregate in the roofing shingles **202**. In other embodiments, the aggregate removal unit **204** may be operable to remove at least about 96 wt. %, or at least about 97 wt. % or at least 98 wt. % or at least 99 wt. % of the total weight of aggregate in the roofing shingles **202**.

(69) Separation of Fiber Step (**106**) in Fiber Separation Unit (**206**)

(70) As described above, in step **106**, fiber may be separated from the asphalt/fiber/filler mixture **112** by adding a solvent **114** to the asphalt/fiber/filler mixture **112** to form the asphalt/fiber/filler solvent slurry and machine pressing the slurry to remove fiber from the slurry to produce an asphalt/filler/solvent mixture **124** and a fiber product **116**. In the embodiment shown in FIG. 2, this separation may be accomplished in the fiber separation unit **236** by adding solvent **230** to the asphalt/fiber/filler mixture **212** in mixing tank **232** to form an asphalt/fiber/filler/solvent slurry **234** and separating fiber from the asphalt/fiber/filler/solvent slurry **234** in the fiber separator **236** to produce an asphalt/filler/solvent mixture **246** and fiber product **214**. In one embodiment, step **106** is performed in the fiber separation unit **206** at ambient temperature.

(71) The mixing tank **232** may be any suitable container or vessel configured to receive and mix the solvent **230** and asphalt/fiber/filler mixture **212** to form the asphalt/fiber/filler solvent slurry **234** and holding the slurry therein. The mixing tank **232** may include any mixing device suitable for mixing described above, such as a paddle, impeller or a recirculation pump to improve the contact between the solvent **230** and asphalt/fiber/filler mixture **212**.

(72) The solvent **230** may be any suitable solvent or blend of more than one solvent. In one embodiment, the solvent **230** may be at least one solvent that is miscible with asphalt. The solvent



**230** may perform some or all of the beneficial functions as outlined below when introduced into the mixing tank **232**. Firstly, the solvent **230** may act as a release agent to strip or remove asphalt coating the fiber in the asphalt/fiber/filler mixture **212** (i.e. the fiber in the asphalt/fiber/filler/solvent slurry **234** may become substantially free from adhered asphalt). As will be explained in more detail below, the solvent **230** may also release filler that is entrained within the asphalt and strip or remove asphalt that is coating the filler in the asphalt/fiber/filler mixture **212** (i.e. the filler in the asphalt/fiber/filler/solvent slurry **234** may become substantially free from adhered asphalt). The solvent **230** may also act as a co-solvent/diluent for the asphalt/fiber/filler mixture **212** which will beneficially reduce the viscosity of the asphalt/fiber/filler/solvent slurry **234**. As such, the asphalt/fiber/filler/solvent slurry **234** may include a liquid phase that is a solution of solvent and asphalt with a solid phase of fiber and filler. Furthermore, the solvent **230** may be selected from a group of solvents having a boiling point that enables easier solvent separation in step **108**.

(73) In one embodiment, the solvent **230** may comprise an aromatic solvent, which refers to a solvent comprising at least one aryl group. The term “aryl” as used herein, whether it is used alone or a part of another group refers to cyclic groups that contain at least one aromatic ring. In an embodiment, the aromatic solvent is benzene, toluene, ortho-xylene, meta-xylene, para-xylene, ethylbenzene or trimethylbenzene.

(74) In another embodiment, the solvent **230** comprises an aliphatic solvent or blend of more than one aliphatic solvent such as a straight or branched chain C.sub.4-C.sub.30 alkane or C.sub.4-C.sub.40 Olefin. In one embodiment, the aliphatic solvent, is butane, pentane, cyclopentane, hexane, cyclohexane, heptane, octane, nonane, decane, undecane or dodecane, or a terpene such as limonene. In other embodiments the aliphatic solvent may be any suitable blend of more than one aliphatic solvents such as gasoline, diesel, petroleum distillate, petroleum ether, mineral spirits, naphtha, kerosene or turpentine.

(75) In another embodiment, the solvent **230** comprises a halogenated solvent, that is a solvent containing at least one halogen atom, such as dichloromethane, 1,1,1-trichloroethylene, tetrachloroethylene, n-propylbromide, chlorohexane, carbon tetrachloride or chloroform.

(76) In another embodiment, the solvent **230** comprises a suitable alcohol, such as a straight or branched chain C.sub.1-C.sub.10 alcohol or mixture thereof. In an embodiment the C.sub.1-C.sub.10 alcohol is ethanol, butanol, propanol, isopropanol (IPA). The alcohol may comprise an aromatic alcohol, which refers to an alcohol comprising an aryl group as defined above, such as benzyl alcohol.

(77) In an embodiment, the solvent **230** comprises an ether, such as tetrahydrofuran, diethyl ether, 1,2-dioxane, 1,3-dioxane or 1,4-dioxane, methoxybenzene.

(78) In another embodiment, the solvent **230** comprises a ketone, for example a C.sub.3-C.sub.12 ketone such as acetone, methyl ethyl ketone (MEK), methyl isobutyl ketone, or methyl acetate.

(79) In another embodiment, the solvent **230** is carbon disulfide.

(80) The solvent **230** may be added to the mixing tank **232** in any suitable mass fraction relative to the asphalt/fiber/filler mixture **212**. For example, the mass fraction of solvent **230** that is added to the asphalt/fiber/filler mixture **212** may be selected such that substantially all of the asphalt in the asphalt/fiber/filler mixture **212** coating the fiber and/or filler is released so substantially all of the asphalt in the asphalt/fiber/filler/solvent slurry **234** is in the liquid phase. Further, the solvent **230** may be added such that the asphalt/fiber/filler/solvent slurry **234** is flowable at ambient temperature.

(81) In one embodiment, the mass fraction of solvent **230** added to the asphalt/fiber/filler mixture **212** may be in the range of about 15-50 wt. % relative to the total weight of the asphalt/fiber/filler mixture **212**. In another embodiment, the amount of the solvent **230** added to the asphalt/fiber/filler mixture is an amount of greater than about 15 wt. % relative to total weight of the asphalt/fiber/filler mixture **212**, for example, greater than about 20 wt. %, greater than about 25 wt.

%, greater than about 26 wt. %, greater than about 27 wt. %, greater than about 28 wt. %, greater than about 29 wt. %, greater than about 30 wt. %, greater than about 31 wt. %, greater than about 32 wt. %, greater than about 33 wt. %, greater than about 34 wt. %, greater than about 35 wt. %, greater than about 40 wt. %, greater than about 45 wt. %, or greater than about 50 wt. %, relative to the total weight of the asphalt/fiber/filler mixture **212**.

(82) The asphalt/fiber/filler/solvent slurry **234** is then sent to and received by the fiber separator **236** to separate the fiber from the slurry. The fiber separator **236** may be any suitable piece of equipment or apparatus that is operable to separate fiber from the asphalt/fiber/filler/solvent slurry **234**, such as a machine press (mechanical press) or a filter press. For example, the fiber separator **236** may be a rotary press, belt press, hydraulic press, piston press, hydrocyclone or a centrifuge.

(83) In one embodiment, the fiber separator **236** is a screw press, also commonly referred to as a dewatering screw press, which is operable to separate fiber from the asphalt/fiber/filler/solvent slurry **234**. The screw press is known and may include one or more screws (also known as an Archimedean screw) which is rotatable within a housing. The screw may include a central shaft about which is wound a spiral steel plate. Material, in this case the asphalt/fiber/filler/solvent slurry **234**, may be sent to and received by an inlet of the screw press. As the screw rotates, for example when driven by an electrical motor, the slurry **234** within the housing will move towards the opposite end of the inlet (i.e., discharge end) of the housing. As the slurry **234** moves from the inlet end to the discharge end, the cavity size in which the slurry **234** is contained decreases such that the slurry therein is compressed. This reduction in cavity size may be due to a taper on the central shaft of the screw such that the diameter of the shaft increases towards the discharge end. Additionally or alternately, the separation between the flights of the spiral steel plate may decrease towards the discharge end of the screw press in order to compress the slurry **234** between the flights towards the discharge end.

(84) The housing may be made from a permeable material, such as a screened surface, a perforated sheet, a sintered screen or a wedge wire screen that, as the slurry **234** is compressed therein, the internal pressure generated within the housing forces asphalt and solvent to be discharged through the permeable material. The permeable material may be selected such that substantially only asphalt and solvent will pass through the permeable material and not fiber or other solid particles from the asphalt/fiber/filler/solvent slurry **234**. In this example, the liquid (or filtrate or liquor) passing through the permeable material is the asphalt/filler/solvent mixture **242**.

(85) The remaining solid fiber material, which does not pass through the cylindrical housing is conveyed towards the discharge end of the screw press by the rotational action of the screw and may be recovered at the discharge end as the fiber product **214** commonly called the press cake or filter cake.

(86) In comparison to other fiber separators, a screw press is well suited to process relatively viscous materials, such as the asphalt/fiber/filler/solvent slurry **234**. A screw press may also advantageously operate in continuous manner with a high throughput and is less susceptible to clogging/blockages in comparison to other fiber separators.

(87) In some embodiments, either or both of the screw press or the asphalt/fiber/filler/solvent slurry **234** may be at ambient temperature or at an elevated temperature.

(88) In an embodiment the screw press may be a twin screw press, which includes two opposed, intermeshing screws configured to rotate in opposite directions relative to each other.

(89) In some embodiments, the fiber separator **236** is a hydraulic press. In some embodiments the hydraulic press may have multiple press chambers arranged in parallel. At any time, the position of each of press chambers within their production cycle may be offset from one-another.

(90) The fiber product **214** that is separated from the slurry **234** and recovered from the fiber separator **236** may be substantially free of asphalt. In one embodiment, the fiber product **214** may have less than about 20 wt. % of asphalt, based on the total weight of the fiber product **214**. In other embodiments, the fiber product **214** may have less than about 15 wt. %, or less than about 10

wt. % or less than about 9 wt. % or less than about 8 wt. % or less than about 7 wt. % or less than about 6 wt. % or less than about 5 wt. % or less than about 4 wt. % or less than about 3 wt. % or less than about 2 wt. % or less than about 1 wt. % of asphalt, based on the total weight of the fiber product **214**.

(91) The fibre separator **236** may be configured to separate fiber from slurry **234**, but not to separate filler from slurry **234**. This may be in part due the difference in particle size between the filler and fiber in slurry **234**, whereby the average particle size of the filler is smaller than the particle size of the fiber. As a result of this, the majority of the filler component of slurry **234** will pass through fiber separator **236** and be carried into the asphalt/filler/solvent mixture **242**.

(92) The fiber product **214** that is separated from the slurry **234** and recovered from the fiber separator **236** may therefore be substantially free of filler. It may be advantageous that fiber product is substantially free from filler as it may be challenging to separate a mixture of fiber and filler. Furthermore, the fiber product may have increased applications and value if substantially free of filler. In one embodiment, the fiber product **214** may have less than about 20 wt. % of filler, based on the total weight of the fiber product **214**. In other embodiments, the fiber product **214** may have less than about 20 wt. % of filler, or less than about 15 wt. %, or less than about 10 wt. %, or less than about 9 wt. % or less than about 8 wt. %, or less than about 7 wt. %, or less than about 6 wt. %, or less than about 5 wt. %, or less than about 4 wt. %, or less than about 3 wt. %, or less than about 2 wt. % or less than about 1 wt. % of filler, based on the total weight of the fiber product **214**.

(93) Separation of Filler Step (122) in Fiber Separation Unit (240)

(94) As described above, in step **122**, filler may be separated from the asphalt/filler/solvent mixture **124** to produce an asphalt/solvent mixture **118** and a filler product **126**. In the embodiment shown in FIG. 2, this separation may be accomplished in the filler separation unit **240** by passing the asphalt/filler/solvent mixture **242** through a first filler separator **244** and optionally, a second filler separator **250** to produce the asphalt solvent mixture **216** and filler product **246**.

(95) As explained above, addition of solvent **230** to asphalt/fiber/filler mixture **212** may function to release filler that is entrained within the asphalt and strip or remove asphalt that is coating the filler in the asphalt/fiber/filler mixture **212** (i.e. the filler in the asphalt/fiber/filler/solvent slurry **234** may become substantially free from adhered asphalt). As such, the filler in the asphalt/filler/solvent mixture **242** may be suspended throughout the mixture, although the filler may settle out of asphalt/filler/solvent mixture **242** if asphalt/filler/solvent mixture **242** stagnates.

(96) The first filler separator **244** may be any suitable piece of equipment or apparatus that is operable to separate a portion of the filler from the asphalt/filler/solvent mixture **124** to produce asphalt solvent mixture **216** and filler product **246**.

(97) In some embodiments, first filler separator **244** may be any suitable filtration apparatus such as a machine press (mechanical press), a filter press such as screw press (such as described above), automated self-cleaning filter, rotary press, belt press, hydraulic press, piston press, self cleaning filter, automated backwash filter, cartridge or membrane filter.

(98) In some embodiments, the first filler separator **244** and/or the second filler separator **250** may operate under reduced pressure or under vacuum.

(99) In some embodiments, first filler separator **244** may be a centrifuge, such as disc centrifuge, a stacked disc centrifuge, a decanting centrifuge, a horizontal centrifuge or a filtering centrifuge.

(100) A centrifuge may be well suited to process asphalt/filler/solvent mixture **242**, in part due to the relatively small particles of filler that may be suspended throughout the mixture **242** which may be challenging to remove by other methods. A centrifuge may also advantageously operate in continuous manner with a high throughput and be less susceptible to clogging/blockages.

(101) In some embodiments, first filler separator **244** may be a single stage centrifuge, configured to remove particles with a size of 50 microns and greater. In other embodiments, first filler separator **244** may be a two-stage centrifuge. The first stage of the two-stage centrifuge may be

configured to remove relatively coarse particles of filler, for example filler particles with a size of 200 microns or greater. The second stage of the two stage centrifuge may be configured to remove relative fine particles of filler, for example filler particles with a size of 50 microns or greater. (102) In some embodiments, first filler separator **244** may remove substantially all of the filler particles from asphalt/filler/solvent mixture **242**, down to a particle size of 200 microns or less, or 50 microns or less.

(103) In some embodiments, first filler separator **244** may also remove any remaining fiber particles that may be present in asphalt/filler/solvent mixture **242**, that were not removed in fiber separator.

(104) The filler product **246** that is separated from the asphalt/filler/solvent mixture **242** and recovered from the first filler separator **244** may be substantially free of asphalt. In one embodiment, the filler product **246** may have less than about 20 wt. % of asphalt, based on the total weight of the filler product **214**. In other embodiments, the filler product **246** may have less than about 15 wt. %, or less than about 10 wt. % or less than about 9 wt. % or less than about 8 wt. % or less than about 7 wt. % or less than about 6 wt. % or less than about 5 wt. % or less than about 4 wt. % or less than about 3 wt. % or less than about 2 wt. % or less than about 1 wt. % of asphalt, based on the total weight of the filler product **246**.

(105) In some embodiments, the asphalt/solvent mixture **216** is produced exclusively from first filler separator **244**. In other embodiments, first filler separator **244** may not remove substantially all of the filler from asphalt/filler/solvent mixture **242**, especially with regards to fine particles of filler that may be present. Therefore, in some embodiments an intermediate asphalt/solvent mixture **248** (which has a reduced proportion of filler relative to the asphalt/filler/solvent mixture **242**) produced from first filler separator **244** may be fed to a second filler separator **250**.

(106) Intermediate asphalt/solvent mixture **248** may substantially comprise asphalt and solvent, and be substantially free of filler. In some embodiments, intermediate asphalt/solvent mixture **248** may have less than about 5 wt. %, or less than about 4 wt. % or less than about 3 wt. % or less than about 2 wt. % or less than about 1 wt. % of filler, based on the total weight of intermediate asphalt/solvent mixture **248**.

(107) In some embodiments, first filler separator **244** may be the same piece of equipment or apparatus as second filler separator **250**. For example, first filler separator **244** second filler separator **250** may both be centrifuges.

(108) In some embodiments, second filler separator **250** is a gravity separator, such as a settling tank. The settling tank may be configured to receive a flow of asphalt/filler/solvent mixture **242** and distribute the flow into the inner volume of the settling tank, thereby reducing the velocity of the flow. The settling tank may be configured to allow any filler particles that were not removed in the first filler separator **244** to settle by gravity to a lower portion of the settling tanks. A recycle stream **252**, which may be a slurry having an elevated concentration of filler, is fed from a lower region of the settling tank to first filler separator **244**. Recycle stream **252** is processed in first filler separator **244**, along with asphalt/filler/solvent mixture **242** as described above. Asphalt/solvent mixture **216** is also produced from an upper region, for example as an overflow stream collected by a weir within the settling tank.

(109) In other embodiments, recycle stream **252** may be processed in a separate filler separator, which may be similar to first and second filler separators **244**, **250** described herein.

(110) In some embodiments, second filler separator **250** comprises a single settling tank as described above which produces asphalt solvent mixture **216**, which is fed to one or more storage tanks for storage prior to being fed to solvent separator unit **208**.

(111) In some embodiments, second filler separator **250** comprises multiple settling tanks connected in series. For example second filler separator **250** may comprise multiple settling tanks, for example 2, 3 or 4 settling tanks connected in series.

(112) With reference to FIG. 3, an example embodiment of filler separation unit **240** is depicted

where second filler separator **250** is depicted and comprises a first settling tank **254** and a second settling tank **256**. A first intermediate asphalt/solvent mixture **258** (which may be similar to intermediate asphalt/solvent mixture **248** described above) may be fed to first settling tank **254**, which produces a first recycle stream **260** (which may be similar to recycle stream **252** described above) and a second intermediate asphalt/solvent mixture **262**. First recycle stream **260** may be a slurry having an elevated concentration of filler in comparison to first intermediate asphalt/solvent mixture **258** and second intermediate asphalt/solvent mixture **262**. First recycle stream **260** is fed to first filler separator **244** for processing as described above.

(113) Second intermediate asphalt/solvent mixture **262** is fed to second settling tank **256**, which produces a second recycle stream **264** and asphalt/solvent mixture **216**. Second recycle stream **264** may be a slurry having an elevated concentration of filler in comparison to asphalt/solvent mixture **216**. Second recycle stream **264** may be fed to first filler separator **244** for processing as described above. In some embodiments, a portion or all of second recycle stream **264** may be fed into first settling tank **254**.

(114) The use of second filler separator **250** may have several benefits. Firstly, second filler separator **250** may remove additional filler that is not removed by first filler separator **244**, thereby further reducing the filler concentration of asphalt/solvent mixture **216**. Secondly, in situations where a larger proportion of filler is not removed by first filler separator **244** as filler product **246**, second filler separator **250** may prevent filler undesirably reaching solvent separation unit **208**. This may be caused by, for example, if asphalt/filler/solvent mixture **242** has elevated proportion of filler or first filler separator **244** is not operating optimally. It is beneficial to reduce the filler reaching solvent separator **208**, as filler may cause deposits that may, for example, interfere with the preheater of solvent separator **238**, thereby reducing efficiency.

(115) In some embodiments, first filler separator **244** is a centrifuge and second filler separator **250** is a gravity separator.

(116) In some embodiments, either or all of the first filler separator **244**, second filler separator **250**, asphalt/filler/solvent mixture **242**, intermediate asphalt/solvent mixture **248** or recycle stream **252** may be at ambient temperature or at an elevated temperature.

(117) In some embodiments, filler removal unit **240** may comprise additional filler separators configured to remove filler from an asphalt/solvent/filler stream, which may or may not be the same as first filler separator **244** or second filler separator **250**. For example, filler removal unit **240** may comprise a third filler separator, configured to receive a second intermediate asphalt/solvent mixture from second filler separator **250** and produce an asphalt/solvent mixture and a recycle stream (similar to recycle stream **252** described above) which may be fed either or both of first filler separator **244** or second filler separator **250**.

(118) Filler separation unit **240** may be configured to remove substantially all of the filler from asphalt/filler/solvent mixture **242** and recover the filler as filler product **246**. In some embodiments, more than 80 wt. % of the total weight of filler in the asphalt/filler/solvent mixture **124** is recovered as filler product **246**, or more than 85% wt. %, or more than 90% wt. %, or more than 95% wt. %, or more than 98% wt. % of the total weight of filler in asphalt/filler/solvent mixture **242** is recovered as filler product **246**.

(119) Generally speaking, the filler product **246** will have a liquid (i.e., solvent and asphalt) that is less than the liquid content of the asphalt/filler/solvent mixture **242**. According to one embodiment, the filler product **246** can contain less than about 1 wt. % liquid (e.g., solvent), based on the total weight of the filler product **246**, for example, less than about 2 wt. % liquid, or less than about 4 wt. % liquid, or less than about 6 wt. % liquid, or less than about 8 wt. % liquid, or less than about 10 wt. % liquid, based on the total weight of the a filler product **246**.

(120) Substantially all of the asphalt may be separated from the filler product **246**, such that the filler product **246** is substantially free of asphalt. In one embodiment, the filler product **246** may contain less than about 3 wt. % of asphalt, based on the total weight of the filler product **246**. In

other embodiments, the filler product **246** may contain less than about 2 wt. %, or less than about 1 wt, of asphalt based on the total weight of the filler product **246**.

(121) In some embodiments, filler product **246** may be further processed to remove remaining solvent and and/or asphalt. For example filler product **246** may be washed with solvent and/or dried (i.e., to remove any remaining solvent or water, using any suitable means known to those skilled in the art.)

(122) Substantially all of the filler may be separated from asphalt/filler/solvent mixture **242**, such that the asphalt/solvent mixture **216** is substantially free of filler. In one embodiment, the asphalt/solvent mixture **216** may contain less than about 5 wt. % of filler, based on the total weight of the asphalt/solvent mixture **216**. In other embodiments, the asphalt/solvent mixture **216** may contain less than about 4 wt. %, or less than about 3 wt. %, or less than about 2 wt. %, or less than about 1 wt. % filler, based on the total weight of the asphalt/solvent mixture **216**. Accordingly, the filler removal unit **240** may be operable to remove at least 95 wt. % of the total weight of filler from asphalt/filler/solvent mixture **242**. In other embodiments, the filler removal unit **240** may be operable to remove at least about 96 wt. %, or at least about 97 wt. % or at least 98 wt. % or at least 99 wt. % of the total weight of filler in asphalt/filler/solvent mixture **242**.

(123) In some embodiments, additional solvent, which may be the same as solvent **230** added in fiber separation unit **206** or a different solvent as described herein may be added on one or both of first and second filler separators **244**, **250** to improve the separation of filler. Additional solvent may function to improve separation within the first or second filler separators **244**, **250**, for example by reducing the viscosity of the mixture within, thereby allowing filler that may be suspended to drop out from the liquid phase.

(124) Recovery of Asphalt Step (**108**) in Solvent Separation Unit (**208**)

(125) As described above, in step **108** solvent may be separated from the asphalt/solvent mixture **118** by heating the mixture to separate the solvent from the mixture to produce an asphalt product **120**. In the embodiment shown in FIG. 2, this separation may be accomplished in the solvent separation unit **208** by passing the asphalt/solvent mixture **216** through the solvent separator **238** to produce the asphalt product **218**.

(126) In one embodiment, the solvent separator **238** may be any suitable distillation unit or evaporator such as, for example a fractional distillation unit, a short path distillation unit, a 2-stage distillation unit, a disc and donut distillation unit or a spinning band distillation unit operable to separate solvent from the asphalt/solvent mixture **216**. The solvent separator **238** may operate at atmospheric or reduced pressure as required. In another embodiment, the solvent separator **238** may be an evaporator, such as thin film evaporator, which may include a falling film evaporator or a wiped film evaporator. In another embodiment, the solvent separator **238** may be a heated stirred tank such as a commonly known continuous stirred tank reactor (CSTR).

(127) In other embodiments, the solvent separator operates at atmospheric pressure and at a temperature of about 75° C. or greater. In one embodiment, the solvent separator operates at atmospheric pressure and a temperature of about 77° C.

(128) In one preferred embodiment, the solvent separator **238** is a wiped film evaporator (WFE), also known as a wiped film distillation unit. The WFE may include a vertically orientated cylinder with an internal rotor driven wiper. The wiper may include a single blade or a plurality of stacked blades that may be offset and/or overlap with respect to each other. In an embodiment the WFE may have 32 blades. The cylinder may be externally heated, such as by a surrounding heated jacket. The asphalt/solvent mixture **216** may be introduced at the upper end of the cylinder and the wiper may distribute the mixture to create a thin film of the mixture on the inner surface of the cylinder. As the mixture **216** spirals down the inner surface of the cylinder, the solvent within the mixture is readily evaporated.

(129) In some embodiments the WFE may have a fixed gap rotor (i.e., a rotor with a fixed gap between the blades and the inner surface of the cylinder) with 3, 4, 5, 6, 7, 8 or more blades. In

some embodiments, the blades may extend the full length of the inner surface of the cylinder of the WFE.

(130) The distillate vapor (i.e., solvent) may be condensed and collected in an internal condenser running down the center of the cylinder. In other embodiments, the distillate vapor may flow out of either the top or bottom of the WFE and may be condensed in an external condenser.

(131) The concentrate (i.e., asphalt **118**) does not evaporate under these conditions and will run down the inner surface of the cylinder and be recovered as the asphalt product **218** at the lower end of the cylinder where it may be transferred, for e.g., to a storage tank or rail car or road tanker, for further processing/repurposing.

(132) The WFE may operate at about 10° C. to about 50° C. above the boiling point of the solvent being used and at about 10° C. to about -50° C. below the lowest boiling point component of the asphalt. The WFE may operate under a vacuum which may be least about 0 mmHg up to a slight positive pressure of about 30 psia (i.e., from about 0 atm to about 2 atm). In one example embodiment, when the solvent **230** is toluene, the WFE may operate at a temperature of about 155-165° C. and at atmospheric pressure.

(133) In an embodiment, the WFE operates at a temperature between about 120° C. and about 200° C. and at atmospheric pressure.

(134) The solvent that is condensed and recovered from the solvent separator **236** may be substantially free of asphalt and other impurities and may be recycled back to mixing tank **232**, as shown in FIG. 2.

(135) The asphalt product **218** may be recovered from the solvent separator **238** in high yield and purity and may be substantially free of fiber, filler, solvent and fluid **224**. According to one embodiment, the asphalt product **218** can contain less than about 1 wt. % of fiber and/or filler and/or solvent and/or fluid **224**, based on the total weight of the asphalt product, for example less than about 2 wt. %, less than about 3 wt. %, less than about 4 wt. % or less than about less than about 5 wt. %, based on the total weight of the asphalt product.

(136) In an embodiment where asphalt/solvent mixture **216** contains a proportion of water and where solvent **230** is toluene, the toluene and water within asphalt/solvent mixture **261** may form an azeotropic mixture. As is known, an azeotropic mixture may have a boiling point that is lower than either of its constituents. As such, depending on the composition of the azeotropic mixture the solvent separator **238** (such as a WFE) may operate at a lower temperature of the boiling point of the pure form water or solvent at the same pressure.

(137) The overall recovery of the asphalt product **218** from the roofing shingles **202** may be highly efficient such that a large proportion of the asphalt that was present in the roofing shingles **202** when the roofing shingles are added to the separation tank **222** is recovered as asphalt product **218**. According to one embodiment, at least about 80 wt. % of the total weight of asphalt in the roofing shingles **202** is recovered as asphalt product **218**, for example at least about 82 wt. %, at least about 84 wt. %, at least about 86 wt. %, at least about 88 wt. %, at least about 90 wt. %, at least about 92 wt. %, at least about 94 wt. %, at least about 96 wt. %, at least about 98 wt. % at least about 98 wt. % of the total weight of asphalt in the roofing shingles **202** is recovered as asphalt product **218**.

(138) In another embodiment, the present disclosure provides a process for recycling asphalt-based roofing materials wherein the units of such a process are completely integrated, and thus the process is of low cost, economical and versatile due to the alternatives and interconnections within their steps. The integrated process is more energy efficient and materials efficient than the individual processes together, and, as such, yields a higher productivity.

(139) According to one embodiment, the integrated process of the present disclosure relates to an integrated process for recycling asphalt-based roofing shingles to produce an aggregate product, a fiber product, a filler product and an asphalt product. The integrated process may include a step of contacting the asphalt-based roofing shingles with at least one pressurized stream of fluid in a separation tank to separate aggregate from the roofing shingles to produce an asphalt/fiber/filler

slurry and the aggregate product as described above. Moisture is then removed from the asphalt/fiber/filler slurry in a dewatering or drying apparatus to produce an asphalt/fiber/filler mixture. The moisture that is removed in the drying apparatus may be recovered and recycled back to the separation tank.

(140) The integrated process also includes a step of adding a solvent to the asphalt/fiber/filler mixture produced above in a mixing tank to produce an asphalt/fiber/filler/solvent slurry. Fiber is separated from the asphalt/fiber/filler/solvent slurry in a fiber separator to produce an asphalt/filler/solvent mixture and the fiber product.

(141) The integrated process also include a step of separating fiber from the asphalt/filler/solvent mixture to produce an asphalt solvent mixture and the filler product.

(142) The integrated process also includes a step of separating solvent from the asphalt/solvent mixture produced above in a solvent separator to produce the asphalt product. Solvent separated from the asphalt/solvent mixture may be recovered and recycled back to the mixing tank.

(143) The integrated process described above may run batch-wise or continuously where roofing shingles are continuously added to the process while the aggregate, fiber and asphalt products are continuously produced and collected. The fluid and solvent that are recovered may be continuously reused within the integrated process as described above such that additional fluid and solvent may not need to be required to be added during continuous operation. In some embodiments a small amount of fluid and/or solvent may need to be added to account for any losses during the process.

(144) Accordingly, the products made in the method, integrated process and system described herein may be suitable for a use in variety of applications. By way of example, the aggregate product may be used in asphalt concrete for paving and road surfaces, in the manufacture of new asphalt-based roofing materials, as a blasting material (or media) in sandblasting and in other general construction materials.

(145) When the roofing shingles include paper fiber, the fiber product may have a high BTU value and may be suitable for use as an engineered fuel. The fiber product may beneficially contain a trace amounts of combustible organics, such as solvent and/or asphalt which may increase the BTU value of the fiber product. In one embodiment, the fiber product may be used as an engineered fuel, such as for a cement production facility.

(146) When the roofing shingles include glass fiber, the fiber product may be incorporated into the production of new glass fiber materials and products. In another embodiment, the fiber product may be used in patching kits for repairing fiber glass structures, such as boats and kayaks. In one embodiment, the fiber product may be further processed by mechanical grinding or milling to reduce its particle size to a fine powder that may be incorporated as a filler or reinforcing material for products such as artificial wood, cement or asphalt concrete.

(147) The filler product produced herein may be reused as a filler, such as in the production of new roofing shingles or in the textile, construction, agriculture, chemical manufacturing, paint, paper, rubber, glass and plastic industries or as a fire retardant. It may be advantageous to produce a filler product that is substantially free of fiber, as this filler product may be suitable for use in more applications and therefore be of increased value in comparison to a mixture of filler and fiber.

(148) The asphalt product produced herein may be of a similar quality to refined (or virgin) asphalt and may be suitable for any application where refined asphalt is used. For example, the asphalt may be suitable for blending with virgin asphalt for any application where refined asphalt is used. For example, the asphalt product may be used in asphalt concrete for paving and road surfaces, in the manufacture of new asphalt-based roofing materials and sealing and insulating a variety of building materials, such as pipe coatings and carpet tile backing.

(149) Generally speaking, the properties of the asphalt product **218** will be dependent on the properties of the asphalt component of the asphalt-based roofing material used to produce the asphalt product. This may vary as the roofing shingles **102** may comprise a mixture of different types and ages of roofing shingles, which will therefore comprise varying proportions and types of



asphalt. However, the method and system as described herein may produce an asphalt product having similar properties to the asphalt component of the asphalt-based roofing material e.g., roofing shingles **102**.

(150) In an embodiment, the asphalt produced herein may have a penetration grade of between about 8 and about 50 decimillimeters (dmm), as measured by the American Society for Testing and Materials (ASTM) D5-06 standard test method.

(151) In an embodiment, the asphalt produced herein may have a softening point of between about 80° C. and about 120° C. or greater as measured by the ASTM D36-95 standard test method.

(152) In an embodiment, the asphalt produced herein may have a flash point of between about 180° C. and about 300° C. or greater as measured by the ASTM D92-05a standard test method.

(153) In some embodiments, the asphalt product **218** may be suitable for use in the production of new asphalt-based roofing materials. Where the asphalt product **218** is used in the production of new asphalt-based roofing materials the asphalt product **218** may have a flash point of 550° F. or lower.

(154) In some embodiments, the asphalt product **218** may be suitable for use in road applications, i.e., the production of road surfaces. Where the asphalt product **218** is used in road applications the asphalt product **218** may have a flash point of 440° F. or lower.

(155) In an example embodiment, the asphalt product **218** may have a penetration grade of about 7 dmm at 25° C. (as measured by the ASTM D5 standard test method), a softening point by R&B of about 141.5° C. (as measured by the ASTM D36 standard test method), an Ash content of about 8% (as measured by the ASTM D8078 standard test method), a Brookfield Viscosity of 8600 cPs at 200° C., 1980 cPs at 220° C., 650 cPs at 240° C. and 280 cPs at 260° C. (as measured by the ASTM D4402 standard test method).

(156) In an example embodiment, the asphalt product **218** may have a softening point by R&B of about 96.5° C. (as measured by the ASTM D36 standard test method), a flash point by Cleveland Open Cup (COC) of greater than 275° C. (as measured by the ASTM D92 standard test method), a penetration grade of about 13 dmm at 25° C. (as measured by the ASTM D5 standard test method), a Brookfield Viscosity of 515 cPs at 200° C., 265 cPs at 220° C. (as measured by the ASTM D4402 standard test method).

(157) In an example embodiment, the asphalt product **218** may have a softening point of about 269° F., a penetration grade of about 4 dmm at 32° F. and about 6 dmm at 77° F., a flash point of greater than 600° F., 52.4% asphaltenes by HPLC, 8% saturates by HPLC, 22.1% aromatics by HPLC and 17.5% polar aromatics by HPLC.

(158) In an example embodiment, the asphalt product **218** may have a softening point of greater than 285° F., a penetration grade of about 6 dmm at 77° F., a flash point of about 580° F., 44.1% asphaltenes by HPLC, 13.8% saturates by HPLC, 22.8% aromatics by HPLC and 19.3% polar aromatics by HPLC.

(159) In an example embodiment, the asphalt product **218** may have 45.1% asphaltenes by HPLC, 15.8% saturates by HPLC, 26.9% aromatics by HPLC and 12.2% polar aromatics by HPLC.

(160) In an example embodiment, the asphalt product **218** may have 46.4% asphaltenes by HPLC, 10.3% saturates by HPLC, 24.7% aromatics by HPLC and 18.6% polar aromatics by HPLC.

(161) In other embodiments, any of the intermediate products disclosed herein, such as the asphalt/fiber/filler slurry, the asphalt/fiber/filler mixture, the asphalt/fiber/filler/solvent slurry and the asphalt/solvent mixture, may be collected and transported to another location for further processing, which may include the steps described above or different method steps to produce any of the product described above.

(162) For example, in one embodiment, the asphalt/solvent mixture, rather than entering the solvent separator, may be transported, such as by tanker truck, rail or pipeline for further use, storage or processing. The presence of the solvent in the mixture may beneficially act as a diluent to lower the viscosity of the asphalt/solvent mixture simplifying the handling and transport of the mixture,

especially while at lower temperatures. In one embodiment, the asphalt/solvent mixture may be transported to another facility where the solvent may be separated from the mixture by a solvent separator described above to produce an asphalt product.

## EMBODIMENTS

(163) Particular embodiments of the invention include, without limitation, the following: 1. A method of separating fiber and filler from an aggregate-free asphalt-based roofing material, the method comprising: (a) passing a slurry comprising the aggregate-free asphalt-based roofing material and a solvent through a fiber separator to separate fiber from the slurry and produce an asphalt/filler/solvent mixture and a fiber product; (b) passing the asphalt/filler/solvent mixture through a filler separator to separate filler from the asphalt/filler/solvent mixture to produce an asphalt/solvent mixture and a filler product; wherein the aggregate-free asphalt-based roofing material was derived from an asphalt-based roofing material and is substantially free of aggregate. 2. The method of embodiment 1, wherein the slurry is prepared by mixing the aggregate-free asphalt-based roofing material with a solvent. 3. The method of embodiment 2, wherein the solvent is selected from an aromatic solvent, an aliphatic solvent, an alcohol, an ether, a ketone, carbon disulfide and a mixture thereof. 4. The method of any one of embodiments 1 to 3, wherein a mass fraction of solvent mixed with the aggregate-free asphalt-based roofing material is in a range of about 15-50 wt. % relative to the total weight of the slurry. 5. The method of any one of embodiments 1 to 4, wherein (a) comprises machine pressing or filter pressing the slurry in the fiber separator. 6. The method of any one of embodiments 1 to 5, wherein the fiber separator is a rotary press, a belt press, a hydraulic press, a piston press, a hydrocyclone or a screw press. 7. The method of any one of embodiments 1 to 6, wherein the aggregate-free asphalt-based roofing material was obtained by contacting an asphalt-based roofing material with at least one pressurized stream of fluid to remove substantially all aggregate from the asphalt-based roofing material and drying the asphalt-based roofing material. 8. The method of any one of embodiments 1 to 7, wherein the filler product is substantially free of fiber. 9. The method of any one of embodiments 1 to 8, wherein the filler product comprises less than 10 wt. % of the asphalt/solvent mixture. 10. The method of any one of embodiments 1 to 9, wherein (b) comprises gravity separating, machine pressing or filter pressing the asphalt/filler/solvent mixture in the filler separator. 11. The method of any one of embodiments 1 to 9, wherein the filler separator comprises a machine press, gravity separator, automated self-cleaning filter, rotary press, belt press, hydraulic press, piston press, centrifuge, self cleaning filter, automated backwash filter, cartridge filter, membrane filter or filter press. 12. The method of embodiment 11, wherein the centrifuge comprises a disc centrifuge, a stacked disc centrifuge, a decanting centrifuge, a horizontal centrifuge or a filtering centrifuge. 13. The method of any one of embodiments 1 to 12, where the filler separator is operated under reduced pressure. 14. The method of any one of embodiments 1 to 13, wherein the filler separator comprises a first filler separator and a second filler separator. 15. The method of embodiment 14 wherein the first filler separator is a centrifuge and the second filler separator is a gravity separator, wherein the gravity separator receives an intermediate asphalt/solvent mixture from the centrifuge and produces the asphalt/solvent mixture and a recycle stream, which is fed to the centrifuge. 16. The method of embodiment 15, wherein gravity separator comprises a plurality of gravity separators arranged in series. 17. The method of any one of embodiments 1 to 16, wherein the filler comprises limestone. 18. A method of separating filler from an asphalt/filler/solvent mixture, the method comprising: (a) passing the asphalt/filler/solvent mixture through a filler separator to separate the filler from the asphalt and solvent; (b) removing a filler product from the filler separator. wherein the asphalt/filler/solvent mixture was derived from an asphalt-based roofing material and is substantially free of aggregate and fiber. 19. The method of embodiment 18, wherein the asphalt/filler/solvent mixture is prepared by mixing a substantially de-aggregated asphalt-based roofing material with a solvent. 20. The method of embodiment 18 or 19, wherein the

solvent is selected from an aromatic solvent, an aliphatic solvent, an alcohol, an ether, a ketone, carbon disulfide and a mixture thereof. 21. The method of embodiment 19 or 20, wherein a mass fraction of solvent mixed with the substantially de-aggregated asphalt-based roofing material is in a range of about 15-50 wt. % relative to the total weight of the slurry. 22. The method of any one of embodiments 18 to 21, wherein (a) comprises gravity separating, machine pressing or filter pressing the asphalt/filler/solvent mixture in the filler separator. 23. The method of any one of embodiments 18 to 21, wherein the filler separator comprises a machine press, gravity separator, automated self-cleaning filter, rotary press, belt press, hydraulic press, piston press, centrifuge, self cleaning filter, automated backwash filter, cartridge filter, membrane filter or filter press. 24. The method of embodiment 23, wherein the centrifuge comprises a disc centrifuge, a stacked disc centrifuge, a decanting centrifuge, a horizontal centrifuge or a filtering centrifuge. 25. The method of any one of embodiments 18 to 24, where the filler separator is operated under reduced pressure. 26. The method of any one of embodiments 18 to 25, wherein the filler separator comprises a first filler separator and a second filler separator. 27. The method of embodiment 26 wherein the first filler separator is a centrifuge and the second filler separator is a gravity separator, wherein the gravity separator receives an intermediate asphalt/solvent mixture from the centrifuge and produces the asphalt/solvent mixture and a recycle stream, which is fed to the centrifuge. 28. The method of embodiment 27, wherein gravity separator comprises a plurality of gravity separators arranged in series. 29. The method of any one of embodiments 18 to 28, wherein the filler comprises limestone. 30. A system for producing at least an asphalt product from an asphalt-based roofing material containing a plurality of roofing shingles, the system comprising: (a) an aggregate removal unit operable to remove substantially all aggregate from the asphalt-based roofing material to produce an aggregate-free asphalt/fiber/filler mixture; (b) a fiber separation unit operable to mix the aggregate-free asphalt/fiber/filler mixture with a solvent to produce a slurry and to remove substantially all fiber from the slurry to produce an asphalt/filler/solvent mixture; (c) a filler separation unit operable to separate substantially all filler from the asphalt/filler/solvent mixture to produce an asphalt/solvent mixture; (d) a solvent separation unit operable to separate substantially all solvent from the asphalt/solvent mixture to produce an asphalt product. 31. The system of embodiment 30, wherein the aggregate removal unit comprises a separation tank configured to receive and combine the asphalt-based roofing material and at least one or more pressurized streams of a first fluid and to agitate or pulse a mixture of aggregate, a second fluid and the aggregate-free asphalt/fiber/filler mixture. 32. The system of embodiment 31, wherein the aggregate removal unit further comprises a dewatering or drying apparatus configured to remove moisture from the asphalt/fiber/filler mixture. 33. The system of any one of embodiments 30 to 32, wherein the fiber separation unit comprises a mixing tank configured to receive and combine the aggregate-free asphalt/fiber/filler mixture and a solvent and produce an asphalt/fiber/filler/solvent slurry. 34. The system of embodiment 33, wherein the fiber separation unit further comprises a fiber separator configured to receive the asphalt/fiber/filler/solvent slurry and separate fiber from the asphalt/fiber/filler/solvent slurry and produce the asphalt/filler/solvent mixture and a fiber product. 35. The system of any one of embodiments 30 to 34, wherein the filler separation unit comprises a filler separator configured to receive the asphalt/filler/solvent mixture and separate filler from the asphalt/filler/solvent mixture and produce the asphalt/solvent mixture and a filler product. 36. The system of embodiment 35, wherein the filler separator comprises a gravity separator, an enhanced gravity separator, a machine press or a filter press. 37. The system of embodiment 36, wherein the filler separator comprises an automated self-cleaning filter, rotary press, belt press, hydraulic press, piston press, centrifuge, self cleaning filter, automated backwash filter, cartridge filter, membrane filter or filter press. 38. The system of embodiment 37, wherein the centrifuge comprises a disc centrifuge, a stacked disc centrifuge, a decanting centrifuge, a horizontal centrifuge or a filtering centrifuge. 39. The system of any one of embodiments 30 to 38, where the filler separator is operated under reduced pressure. 40. The system of any one of

embodiments 35 to 39, wherein the filler separator comprises a first filler separator and a second filler separator. 41. The system of embodiment 40, wherein the first filler separator is a centrifuge and the second filler separator is a gravity separator, wherein the gravity separator receives an intermediate asphalt/solvent mixture from the centrifuge and produces the asphalt/solvent mixture and a recycle stream, which is fed to the centrifuge. 42. The system of embodiment 41 wherein gravity separator comprises a plurality of gravity separators arranged in series. 43. The system of any one of embodiments 30 to 42, wherein the solvent separation unit comprises a solvent separator configured to receive the asphalt/solvent mixture and heat the mixture to separate the solvent from the mixture and produce the asphalt product. 44. The system of embodiment 43, wherein the solvent separation unit further comprises a condenser configured to recover the solvent separated from the mixture. 45. The system of any one of embodiments 30 to 44, further comprising a pretreatment unit comprising a grinder operable to reduce the particle size of the asphalt-based roofing material and a feed system to deliver the asphalt-based roofing material to the aggregate removal unit. 46. The system of any one of embodiments 30 to 45, wherein the asphalt product is substantially free of aggregate, fiber and filler.

(164) Although making and using various embodiments of the present disclosure have been described in detail above, it should be appreciated that the present disclosure provides many applicable inventive concepts that can be embodied in a wide variety of specific contexts. The specific embodiments discussed herein are merely illustrative of specific ways to make and use the invention, and do not delimit the scope of the invention.

## Claims

1. A method of separating fiber and filler from an aggregate-free asphalt-based roofing material, the method comprising: (a) passing a slurry comprising the aggregate-free asphalt-based roofing material and a solvent through a fiber separator to separate fiber from the slurry and produce an asphalt/filler/solvent mixture and a fiber product; and (b) passing the asphalt/filler/solvent mixture through a filler separator to separate filler from the asphalt/filler/solvent mixture to produce an asphalt/solvent mixture and a filler product; wherein the aggregate-free asphalt-based roofing material was derived from an asphalt-based roofing material and is substantially free of aggregate.
2. The method of claim 1, wherein the slurry is prepared by mixing the aggregate-free asphalt-based roofing material with a solvent.
3. The method of claim 1, wherein (a) comprises machine pressing or filter pressing the slurry in the fiber separator.
4. The method of claim 1, wherein the fiber separator is a rotary press, a belt press, a hydraulic press, a piston press, a hydrocyclone or a screw press.
5. The method of claim 1, wherein the aggregate-free asphalt-based roofing material was obtained by contacting an asphalt-based roofing material with at least one pressurized stream of fluid to remove substantially all aggregate from the asphalt-based roofing material and drying the asphalt-based roofing material.
6. The method of claim 1, wherein the filler product is substantially free of fiber.
7. The method of claim 1, wherein the filler product comprises less than 10 wt. % of the asphalt/solvent mixture.
8. The method of claim 1, wherein (b) comprises gravity separating, machine pressing or filter pressing the asphalt/filler/solvent mixture in the filler separator.
9. The method of claim 1, wherein the filler separator comprises a machine press, gravity separator, automated self-cleaning filter, rotary press, belt press, hydraulic press, piston press, centrifuge, self cleaning filter, automated backwash filter, cartridge filter, membrane filter or filter press.
10. The method of claim 9, wherein the centrifuge comprises a disc centrifuge, a stacked disc centrifuge, a decanting centrifuge, a horizontal centrifuge or a filtering centrifuge.

11. The method of claim 1, wherein the filler separator comprises a first filler separator and a second filler separator and the first filler separator is a centrifuge and the second filler separator is a gravity separator, wherein the gravity separator receives an intermediate asphalt/solvent mixture from the centrifuge and produces the asphalt/solvent mixture and a recycle stream, which is fed to the centrifuge.
12. The method of claim 11, wherein gravity separator comprises a plurality of gravity separators arranged in series.
13. The method of claim 1, wherein the filler comprises limestone.
14. A method of separating filler from an asphalt/filler/solvent mixture, the method comprising: (a) passing the asphalt/filler/solvent mixture through a filler separator to separate the filler from the asphalt and solvent; and (b) removing a filler product from the filler separator; wherein the asphalt/filler/solvent mixture was derived from an asphalt-based roofing material and is substantially free of aggregate and fiber.
15. The method of claim 14, wherein the asphalt/filler/solvent mixture is prepared by mixing a substantially de-aggregated asphalt-based roofing material with a solvent.
16. The method of claim 14, wherein (a) comprises gravity separating, machine pressing or filter pressing the asphalt/filler/solvent mixture in the filler separator.
17. The method of claim 14, wherein the filler separator comprises a machine press, gravity separator, automated self-cleaning filter, rotary press, belt press, hydraulic press, piston press, centrifuge, self cleaning filter, automated backwash filter, cartridge filter, membrane filter or filter press.
18. The method of claim 17, wherein the centrifuge comprises a disc centrifuge, a stacked disc centrifuge, a decanting centrifuge, a horizontal centrifuge or a filtering centrifuge.
19. The method of claim 14, wherein the filler separator comprises a first filler separator and a second filler separator and the first filler separator is a centrifuge and the second filler separator is a gravity separator, wherein the gravity separator receives an intermediate asphalt/solvent mixture from the centrifuge and produces the asphalt/solvent mixture and a recycle stream, which is fed to the centrifuge.
20. The method of claim 19, wherein gravity separator comprises a plurality of gravity separators arranged in series.
21. The method of claim 14, wherein the filler comprises limestone.
22. A system for producing at least an asphalt product from an asphalt-based roofing material containing a plurality of roofing shingles, the system comprising: (a) an aggregate removal unit operable to remove substantially all aggregate from the asphalt-based roofing material to produce an aggregate-free asphalt/fiber/filler mixture; (b) a fiber separation unit operable to mix the aggregate-free asphalt/fiber/filler mixture with a solvent to produce a slurry and to remove substantially all fiber from the slurry to produce an asphalt/filler/solvent mixture; (c) a filler separation unit operable to separate substantially all filler from the asphalt/filler/solvent mixture to produce an asphalt/solvent mixture; and (d) a solvent separation unit operable to separate substantially all solvent from the asphalt/solvent mixture to produce an asphalt product.
23. The system of claim 22, wherein the aggregate removal unit comprises a separation tank configured to receive and combine the asphalt-based roofing material and at least one or more pressurized streams of a first fluid and to agitate or pulse a mixture of aggregate, a second fluid and the aggregate-free asphalt/fiber/filler mixture.
24. The system of claim 22, wherein the filler separation unit comprises a filler separator configured to receive the asphalt/filler/solvent mixture and separate filler from the asphalt/filler/solvent mixture and produce the asphalt/solvent mixture and a filler product.
25. The system of claim 24, wherein the filler separator comprises a gravity separator, an enhanced gravity separator, a machine press or a filter press.
26. The system of claim 25, wherein the filler separator comprises a machine press, gravity

separator, automated self-cleaning filter, rotary press, belt press, hydraulic press, piston press, centrifuge, self cleaning filter, automated backwash filter, cartridge filter, membrane filter or filter press.

27. The system of claim 26, wherein the centrifuge comprises a disc centrifuge, a stacked disc centrifuge, a decanting centrifuge, a horizontal centrifuge or a filtering centrifuge.

28. The system of claim 24, wherein the filler separator comprises a first filler separator and a second filler separator and the first filler separator is a centrifuge and the second filler separator is a gravity separator, wherein the gravity separator receives an intermediate asphalt/solvent mixture from the centrifuge and produces the asphalt/solvent mixture and a recycle stream, which is fed to the centrifuge.

29. The system of claim 28 wherein gravity separator comprises a plurality of gravity separators arranged in series.

30. The system of claim 22, wherein the asphalt product is substantially free of aggregate, fiber and filler.

---