

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250267951

Kind Code

A1

Publication Date

August 21, 2025

Inventor(s)

YAMAZAKI; Shunpei et al.

DISPLAY DEVICE

Abstract

A protective circuit includes a non-linear element which includes a gate electrode, a gate insulating layer covering the gate electrode, a first oxide semiconductor layer overlapping with the gate electrode over the gate insulating layer, a channel protective layer overlapping with a channel formation region of the first oxide semiconductor layer, and a pair of a first wiring layer and a second wiring layer whose end portions overlap with the gate electrode over the channel protective layer and in which a conductive layer and a second oxide semiconductor layer are stacked. Over the gate insulating layer, oxide semiconductor layers with different properties are bonded to each other, whereby stable operation can be performed as compared with Schottky junction. Thus, the junction leakage can be reduced and the characteristics of the non-linear element can be improved.

Inventors: YAMAZAKI; Shunpei (Setagaya, JP), AKIMOTO; Kengo (Atsugi, JP), KOMORI; Shigeki (Isehara, JP), UOCHI; Hideki (Atsugi, JP), FUTAMURA; Tomoya (Atsugi, JP), KASAHARA; Takahiro (Atsugi, JP)

Applicant: Semiconductor Energy Laboratory Co., Ltd. (Atsugi-shi, JP)

Family ID: 1000008586829

Appl. No.: 19/201993

Filed: May 08, 2025

Foreign Application Priority Data

JP	2008-241743	Sep. 19, 2008
----	-------------	---------------

Related U.S. Application Data

parent US continuation 18101642 20230126 parent-grant-document US 12300691 child US 19201993

parent US continuation 16931780 20200717 ABANDONED child US 18101642

parent US continuation 16189396 20181113 parent-grant-document US 10756080 child US

16931780
parent US continuation 14700455 20150430 parent-grant-document US 10229904 child US
16189396
parent US continuation 12556695 20090910 parent-grant-document US 9048320 child US
14700455

Publication Classification

Int. Cl.: **H10D89/60** (20250101); **G02F1/133** (20060101); **G02F1/1345** (20060101); **H10D30/67** (20250101); **H10D86/40** (20250101); **H10D86/60** (20250101)

U.S. Cl.:

CPC **H10D89/601** (20250101); **G02F1/133** (20130101); **G02F1/13306** (20130101);
G02F1/1345 (20130101); **G02F1/13452** (20130101); **H10D30/6755** (20250101);
H10D86/423 (20250101); **H10D86/441** (20250101); **H10D86/60** (20250101);
H10D89/811 (20250101);

Background/Summary

TECHNICAL FIELD

[0001] The present invention relates to a display device including an oxide semiconductor.

BACKGROUND ART

[0002] A thin film transistor formed over a flat plate such as a glass substrate is manufactured using amorphous silicon or polycrystalline silicon, as typically seen in a liquid crystal display device. A thin film transistor manufactured using amorphous silicon has low field effect mobility, but such a transistor can be formed over a glass substrate with a larger area. On the other hand, a thin film transistor manufactured using a crystalline silicon has high field effect mobility, but a crystallization step such as laser annealing is necessary and such a transistor is not always suitable for a larger glass substrate.

[0003] In view of the foregoing, attention has been drawn to a technique by which a thin film transistor is manufactured using an oxide semiconductor, and such a transistor is applied to an electronic device or an optical device. For example, Patent Document 1 and Patent Document 2 disclose a technique by which a thin film transistor is manufactured using zinc oxide (ZnO) or an In—Ga—Zn—O based oxide semiconductor as an oxide semiconductor film and such a transistor is used as a switching element or the like of an image display device. [0004] [Patent Document 1] Japanese Published Patent Application No. 2007-123861 [0005] [Patent Document 2] Japanese Published Patent Application No. 2007-96055

DISCLOSURE OF THE INVENTION

[0006] A thin film transistor in which a channel formation region is formed using an oxide semiconductor has characteristics as follows: the operation speed is higher than that of a thin film transistor including amorphous silicon and the manufacturing process is simpler than that of a thin film transistor including polycrystalline silicon. That is, the use of an oxide semiconductor makes it possible to manufacture a thin film transistor with high field effect mobility even at low temperatures of 300° C. or lower.

[0007] In order to take advantage of such features of a display device including an oxide semiconductor, which is superior in operating characteristics and capable of manufacture at low temperatures, a protective circuit and the like including suitable structures are necessary. Moreover,

it is important to ensure the reliability of the display device including an oxide semiconductor. [0008] An object of one embodiment of the present invention is to provide a structure which is suitable for a protective circuit.

[0009] In a display device intended for a variety of purposes manufactured by stacking, in addition to an oxide semiconductor, an insulating film and a conductive film, an object of one embodiment of the present invention is to enhance the function of a protective circuit and stabilize the operation.

[0010] One embodiment of the present invention is a display device in which a protective circuit is formed using a non-linear element including an oxide semiconductor. This non-linear element includes a combination of oxide semiconductors with different oxygen contents.

[0011] One illustrative embodiment of the present invention is a display device which includes scan lines and signal lines provided over a substrate having an insulating surface so as to intersect with each other, a pixel portion in which pixel electrodes are arranged in matrix, and a non-linear element formed from an oxide semiconductor in a region outside the pixel portion. The pixel portion includes a thin film transistor in which a channel formation region is formed in a first oxide semiconductor layer. The thin film transistor in the pixel portion includes a gate electrode connected to the scan line, a first wiring layer which is connected to the signal line and which is in contact with the first oxide semiconductor layer, and a second wiring layer which is connected to the pixel electrode and which is in contact with the first oxide semiconductor layer. Moreover, the non-linear element is provided between the pixel portion and a signal input terminal disposed at the periphery of the substrate. The non-linear element includes a gate electrode, a gate insulating layer covering the gate electrode, a first oxide semiconductor layer overlapping with the gate electrode over the gate insulating layer, a channel protective layer covering with a channel formation region of the first oxide semiconductor layer, and a first wiring layer and a second wiring layer whose end portions overlap with the gate electrode over the channel protective layer and in which a conductive layer and a second oxide semiconductor layer are stacked. The gate electrode of the non-linear element is connected to the scan line or the signal line and the first wiring layer or the second wiring layer of the non-linear element is connected to the gate electrode via a third wiring layer so that the potential of the gate electrode is applied to the first wiring layer or the second wiring layer.

[0012] One illustrative embodiment of the present invention is a display device which includes scan lines and signal lines provided over a substrate having an insulating surface so as to intersect with each other, a pixel portion including pixel electrodes arranged in matrix, and a protective circuit in a region outside the pixel portion. The pixel portion includes a thin film transistor in which a channel formation region is formed in a first oxide semiconductor. The thin film transistor in the pixel portion includes a gate electrode connected to the scan line, a first wiring layer which is connected to the signal line and which is in contact with the first oxide semiconductor layer, and a second wiring layer which is connected to the pixel electrode and which is in contact with the first oxide semiconductor layer. In the region outside the pixel portion, a protective circuit for connecting the scan line and a common wiring to each other and a protective circuit for connecting the signal line and a common wiring to each other are provided. The protective circuit includes a non-linear element which includes a gate electrode, a gate insulating layer covering the gate electrode, a first oxide semiconductor layer overlapping with the gate electrode over the gate insulating layer, a channel protective layer covering with a channel formation region of the first oxide semiconductor layer, and a first wiring layer and a second wiring layer whose end portions overlap with the gate electrode over the channel protective layer and in which a conductive layer and a second oxide semiconductor layer are stacked. Moreover, the first wiring layer or the second wiring layer of the non-linear element is connected to the gate electrode via a third wiring layer.

[0013] Here, the first oxide semiconductor layer includes oxygen at higher concentration than the second oxide semiconductor layer. That is, the first oxide semiconductor layer is oxygen-excess type, while the second oxide semiconductor layer is oxygen-deficiency type. The first oxide

semiconductor layer has lower electrical conductivity than the second oxide semiconductor layer. The first oxide semiconductor layer and the second oxide semiconductor layer have non-single-crystal structures, and include at least an amorphous component. In addition, the second oxide semiconductor layer includes a nanocrystal in an amorphous structure in some cases.

[0014] Note that the ordinal numbers such as “first” and “second” in this specification are used for convenience and do not denote the order of steps and the stacking order of layers. In addition, the ordinal numbers in this specification do not denote particular names which specify the invention.

[0015] According to one embodiment of the present invention, a display device having a structure suitable for a protective circuit can be provided by forming the protective circuit with use of a non-linear element including an oxide semiconductor. In the connection structure between the first oxide semiconductor layer of the non-linear element and the wiring layers, the provision of the region which is bonded with the second oxide semiconductor layer, which has higher electrical conductivity than the first oxide semiconductor layer, allows stable operation as compared with a case of using only metal wirings. Accordingly, the function of the protective circuit is enhanced and the operation can be made stable.

Description

BRIEF DESCRIPTION OF DRAWINGS

[0016] In the accompanying drawings:

[0017] FIG. 1 illustrates a positional relationship between a pixel portion and protective circuits including signal input terminals, scan lines, signal lines, and non-linear elements in a display device;

[0018] FIG. 2 illustrates an example of a protective circuit;

[0019] FIG. 3 illustrates an example of a protective circuit;

[0020] FIGS. 4A and 4B are plan views illustrating an example of a protective circuit;

[0021] FIG. 5 is cross-sectional views illustrating an example of a protective circuit;

[0022] FIGS. 6A and 6B are plan views illustrating an example of a protective circuit;

[0023] FIGS. 7A and 7B are plan views illustrating an example of a protective circuit;

[0024] FIGS. 8A to 8C are cross-sectional views illustrating a process for manufacturing a protective circuit;

[0025] FIGS. 9A to 9C are cross-sectional views illustrating a process for manufacturing a protective circuit;

[0026] FIG. 10 is a cross-sectional view of electronic paper;

[0027] FIGS. 11A and 11B are each a block diagram of a semiconductor device;

[0028] FIG. 12 illustrates a structure of a signal line driver circuit;

[0029] FIG. 13 is a timing chart of operation of a signal line driver circuit;

[0030] FIG. 14 is a timing chart of operation of a signal line driver circuit;

[0031] FIG. 15 is a diagram illustrating a structure of a shift register;

[0032] FIG. 16 illustrates a connection structure of a flip-flop of FIG. 15;

[0033] FIGS. 17A1 and 17A2 are top views and FIG. 17B is a cross-sectional view, which illustrate a semiconductor device of Embodiment 6;

[0034] FIG. 18 is a cross-sectional view illustrating a semiconductor device of Embodiment 6;

[0035] FIG. 19 illustrates an equivalent circuit of a pixel in a semiconductor device of Embodiment 7;

[0036] FIGS. 20A to 20C each illustrate a semiconductor device of Embodiment 7;

[0037] FIG. 21A is a top view and FIG. 21B is a cross-sectional view, both describing a semiconductor device of Embodiment 7;

[0038] FIGS. 22A and 22B illustrate examples of applications of electronic paper;

[0039] FIG. 23 is an external view illustrating an example of an electronic book device;
[0040] FIG. 24A is an external view of an example of a television set and FIG. 24B is an external view of an example of a digital photo frame;
[0041] FIGS. 25A and 25B are external views illustrating examples of game machines;
[0042] FIG. 26 is an external view illustrating an example of a mobile phone; and
[0043] FIGS. 27A and 27B are cross-sectional views illustrating an example of a protective circuit.

BEST MODE FOR CARRYING OUT THE INVENTION

[0044] Hereinafter, embodiments of the present invention are described below with reference to the drawings. The present invention is not limited to the description below and it is easily understood by those skilled in the art that the mode and details can be changed variously without departing from the scope and spirit of the present invention. Therefore, the present invention should not be interpreted as being limited to description in the embodiments below. Note that a reference numeral denoting the same portion in all figures is used in common in the structures of the present invention which is explained below.

Embodiment 1

[0045] In Embodiment 1, an example of a display device including a pixel portion and a protective circuit including a non-linear element provided around the pixel portion is described with reference to drawings.

[0046] FIG. 1 illustrates a positional relationship between a pixel portion and protective circuits including signal input terminals, scan lines, signal lines, and non-linear elements in a display device. Over a substrate 10 having an insulating surface, scan lines 13 and signal lines 14 intersect with each other to form a pixel portion 17.

[0047] The pixel portion 17 includes a plurality of pixels 18 arranged in matrix. The pixel 18 includes a pixel transistor 19 connected to the scan line 13 and the signal line 14, a storage capacitor portion 20, and a pixel electrode 21.

[0048] In the pixel structure illustrated here, one electrode of the storage capacitor portion 20 is connected to the pixel transistor 19 and the other electrode is connected to a capacitor line 22. Moreover, the pixel electrode 21 forms one electrode which drives a display element (such as a liquid crystal element, a light-emitting element, or a contrast medium (electronic ink)). The other electrode of such a display element is connected to a common terminal 23.

[0049] A protective circuit is provided between the pixel portion 17, and a terminal 11 and a terminal 12. In Embodiment 1, a plurality of protective circuits are provided. Therefore, even though surge voltage due to static electricity and the like is applied to the scan line 13, the signal line 14, and a capacitor bus line 27, the pixel transistor 19 and the like are not broken. Accordingly, the protective circuit has a structure for releasing charge to a common wiring 29 or a common wiring 28 when surge voltage is applied to the protective circuit.

[0050] In Embodiment 1, a protective circuit 24 is provided on the scan line 13 side, a protective circuit 25 is provided on the signal line 14 side, and a protective circuit 26 is provided on the capacitor bus line 27 side. Needless to say, the structures of the protective circuits are not limited to those above.

[0051] FIG. 2 illustrates an example of the protective circuit. This protective circuit includes a non-linear element 30 and a non-linear element 31 which are arranged in parallel to each other with the scan line 13 therebetween. Each of the non-linear element 30 and the non-linear element 31 includes a two-terminal element such as a diode or a three-terminal element such as a transistor. For example, the non-linear element can be formed through the same steps as the pixel transistor of the pixel portion. For example, characteristics similar to those of a diode can be achieved by connecting a gate terminal to a drain terminal of the non-linear element.

[0052] A first terminal (gate) and a third terminal (drain) of the non-linear element 30 are connected to the scan line 13, and a second terminal (source) thereof is connected to the common wiring 29. A first terminal (gate) and a third terminal (drain) of the non-linear element 31 are

connected to the common wiring **29**, and a second terminal (source) thereof is connected to the scan line **13**. That is, the protective circuit illustrated in FIG. 2 includes two transistors whose rectifying directions are opposite to each other and which connect the scan line **13** and the common wiring **29** to each other. In other words, between the scan line **13** and the common wiring **29** exist the transistor whose rectifying direction is from the scan line **13** to the common wiring **29** and the transistor whose rectifying direction is from the common wiring **29** to the scan line **13**.

[0053] In the protective circuit illustrated in FIG. 2, in a case where the scan line **13** is charged positively or negatively with respect to the common wiring **29** due to static electricity or the like, current flows in a direction that cancels the charge. For example, if the scan line **13** is positively charged, current flows in a direction in which the positive charge is released to the common wiring **29**. Owing to this operation, the electrostatic breakdown or the shift in threshold voltage of the pixel transistor **19** connected to the charged scan line **13** can be prevented. Moreover, it is possible to prevent dielectric breakdown of the insulating film between the charged scan line **13** and another wiring that intersects with the charged scan line **13** with an insulating layer therebetween.

[0054] Note that in FIG. 2, a pair of the non-linear element **30** whose first terminal (gate) is connected to the scan line **13** and the non-linear element **31** whose first terminal (gate) is connected to the common wiring **29** is used; that is, the rectifying directions of the non-linear element **30** and the non-linear element **31** are opposite to each other. The common wiring **29** and the scan line **13** are connected in parallel to each other via the second terminal (source) and the third terminal (drain) of each non-linear element; that is, the non-linear element **30** and the non-linear element **31** are in parallel. As another structure, a non-linear element may be further added in parallel connection, so that the operation stability of the protective circuit may be enhanced. For example, FIG. 3 illustrates a protective circuit including a non-linear element **30a** and a non-linear element **30b**, and a non-linear element **31a** and a non-linear element **31b**, which is provided between the scan line **13** and the common wiring **29**. This protective circuit includes four non-linear elements in total: two non-linear elements (**30b** and **31b**), a first terminal (gate) of each of which is connected to the common wiring **29** and two non-linear elements (**30a** and **31a**), a first terminal (gate) of each of which is connected to the scan line **13**. That is to say, two pairs of non-linear elements are connected between the common wiring **29** and the scan line **13**, each pair including two non-linear elements provided so that their rectifying directions are opposite to each other. In other words, between the scan line **13** and the common wiring **29**, there are two transistors the rectifying direction of each of which is from the scan line **13** to the common wiring **29** and two transistors the rectifying direction of each of which is from the common wiring **29** to the scan line **13**. When the common wiring **29** and the scan line **13** are connected to each other with the four non-linear elements in this manner, it is possible to prevent, even if surge voltage is applied to the scan line **13** and moreover even if the common wiring **29** is charged by static electricity or the like, the charge from directly flowing through the scan line **13**. Note that FIG. 6A illustrates an example in which four non-linear elements **740a**, **740b**, **740c** and **740d** are provided over a substrate and FIG. 6B is an equivalent circuit diagram thereof. Reference numeral **650** is a scan line, and reference numeral **651** is a common wiring.

[0055] FIG. 7A illustrates an example of a protective circuit which is formed using an odd number of non-linear elements over a substrate, and FIG. 7B is an equivalent circuit diagram thereof. In this circuit, a non-linear element **730b** and a non-linear element **730a** are connected to a non-linear element **730c** as switching elements. By the serial connection of the non-linear elements in this manner, instantaneous load applied to the non-linear elements of the protective circuit can be deconcentrated. Reference numeral **650** is a scan line, and reference numeral **651** is a common wiring.

[0056] FIG. 2 illustrates the protective circuit which is provided on the scan line **13** side; however, a protective circuit with a similar structure can be provided on the signal line **14** side. FIG. 4A is a plan view illustrating an example of a protective circuit and FIG. 4B is an equivalent circuit

diagram thereof. FIGS. 5A and 5B are cross-sectional views taken along line Q1-Q2 of FIG. 4A. A structure example of the protective circuit is described below with reference to FIGS. 4A and 4B and FIGS. 5A and 5B.

[0057] The non-linear element **170a** and the non-linear element **170b** include a gate electrode **101** and a gate electrode **16**, respectively, which are formed using the same layer as the scan line **13**. A gate insulating layer **102** is formed over the gate electrode **101** and the gate electrode **16**. A first oxide semiconductor layer **103** is formed over the gate insulating layer **102**, and a channel protective layer is formed over the gate electrode **101** with the first oxide semiconductor layer **103** therebetween. Further, a first wiring layer **38** and a second wiring layer **39** are provided over the channel protective layer so as to face each other. The gate insulating layer **102** and the channel protective layer are formed of an oxide such as silicon oxide or aluminum oxide. Note that the non-linear element **170a** and the non-linear element **170b** have the same structure in the main portion.

[0058] The first oxide semiconductor layer **103** is provided so as to cover the gate electrode **101** with the gate insulating film therebetween, below the first wiring layer **38** and the second wiring layer **39** which are opposed to each other. That is, the first oxide semiconductor layer **103** is provided so as to overlap with the gate electrode **101** and be in contact with a top face of the gate insulating layer **102**, and bottom faces of second oxide semiconductor layers **104a** and **104b**. Here, the first wiring layer **38** has a structure in which the second oxide semiconductor layer **104a** and the conductive layer **105a** are stacked in that order from the first oxide semiconductor layer **103** side and the second wiring layer **39** has a structure in which the second oxide semiconductor layer **104b** and the conductive layer **105b** are stacked in that order from the first oxide semiconductor layer **103** side.

[0059] The first oxide semiconductor layer **103** has higher oxygen concentration than the second oxide semiconductor layers (**104a** and **104b**). In other words, the first oxide semiconductor layer **103** is oxygen-excess type, while the second oxide semiconductor layers (**104a** and **104b**) are oxygen-deficiency type. Since the donor-type defects can be reduced by increasing the oxygen concentration of the first oxide semiconductor layer **103**, there are advantageous effects of longer carrier lifetime and higher mobility. On the other hand, when the oxygen concentration of the second oxide semiconductor layers (**104a** and **104b**) is made lower than that of the first oxide semiconductor layer **103**, the carrier concentration can be increased and the second oxide semiconductor layers (**104a** and **104b**) can be utilized for forming a source region and a drain region.

[0060] As for the structure of the oxide semiconductor, the first oxide semiconductor layer **103** is a non-single-crystal oxide semiconductor layer including In, Ga, Zn and O, and has at least an amorphous component and the second oxide semiconductor layers (**104a** and **104b**) are each a non-single-crystal oxide semiconductor layer including In, Ga, Zn and O, and include a nanocrystal in a non-single-crystal structure in some cases. Then, the first oxide semiconductor layer **103** has characteristics that the electrical conductivity thereof is lower than that of the second oxide semiconductor layers (**104a** and **104b**). Therefore, the second oxide semiconductor layers (**104a** and **104b**) in the non-linear element **170a** and the non-linear element **170b** of Embodiment 1 can have functions similar to those of a source region and a drain region of a transistor. The second oxide semiconductor layer **104a** serving as a source region and the second oxide semiconductor layer **104b** serving as a drain region have n-type conductivity and the activation energy (AE) of from 0.01 eV to 0.1 eV, and the second oxide semiconductor layers (**104a** and **104b**) can also be called n.sup.+ regions.

[0061] The first oxide semiconductor layer **103** and the second oxide semiconductor layers (**104a** and **104b**) are formed from zinc oxide (ZnO) typically, or an oxide semiconductor including In, Ga, and Zn.

[0062] The second oxide semiconductor layers (**104a** and **104b**) are provided in contact with and between the first oxide semiconductor layer **103** and the conductive layers (**105a** and **105b**), and

junction of the oxide semiconductor layers which have different properties is obtained. By provision of the second oxide semiconductor layers (**104a** and **104b**) having higher electrical conductivity than the first oxide semiconductor layer **103**, between the first oxide semiconductor layer and the conductive layers, stable operation becomes possible as compared with Schottky junction formed in the case where the first oxide semiconductor layer and the conductive layers are in direct contact with each other. That is, the thermal stability is increased, so that the stable operation becomes possible. Accordingly, the function of the protective circuit is enhanced and stable operation can be achieved. Moreover, the junction leakage can be reduced and the characteristics of the non-linear element **170a** and the non-linear element **170b** can be improved. [0063] A protective insulating film **107** is provided over the first oxide semiconductor layer **103**. The protective insulating film **107** is formed of an oxide such as silicon oxide or aluminum oxide. Further, by stacking silicon nitride, aluminum nitride, silicon oxynitride, or aluminum oxynitride over silicon oxide or aluminum oxide, the function as the protective film can be enhanced. [0064] In any case, when the protective insulating film **107** being in contact with the first oxide semiconductor layer **103** is an oxide, it is possible to prevent oxygen from being extracted from the first oxide semiconductor layer **103** and prevent the first oxide semiconductor layer **103** from changing into an oxygen-deficiency type. Moreover, by the structure where the first oxide semiconductor layer **103** is not in direct contact with an insulating layer including nitride, it is possible to prevent hydrogen in the nitride from diffusing and causing defects in the first oxide semiconductor layer **103** due to a hydroxyl group or the like.

[0065] The protective insulating film **107** is provided with contact holes **125** and **128** where the scan line **13** formed using the same layer as the gate electrode **101** is connected to a third terminal (drain) of the non-linear element **170a**. This connection is made by a third wiring layer **110** formed from the same material as the pixel electrode of the pixel portion. The third wiring layer **110** is formed from a material which is used for forming a transparent conductive film, for example, from indium tin oxide (ITO), zinc oxide (ZnO), tin oxide (SnO₂), or the like. Thus, the third wiring layer **110** has higher resistance than a wiring formed from a metal material. When the protective circuit includes the wirings including such a resistant component, it is possible to prevent an excessive amount of current from flowing through the non-linear element **170a** from being destroyed.

[0066] Although FIGS. **4A** and **4B** and FIG. **5** illustrate the example of the protective circuit provided for the scan line **13**, a similar protective circuit can be applied to a signal line, a capacitor bus line, or the like.

[0067] According to Embodiment 1, by the provision of the protective circuit including the oxide semiconductor in this manner, a display device having a structure which is suitable for a protective circuit can be provided. Thus, the function of the protective circuit can be enhanced and the operation can be stabilized.

Embodiment 2

[0068] In Embodiment 2, one embodiment of a process for manufacturing a protective circuit illustrated in FIG. **4A** in Embodiment 1 is described with reference to FIGS. **8A** to **8C** and FIGS. **9A** to **9C**. FIGS. **8A** to **8C** and FIGS. **9A** to **9C** are cross-sectional views taken along line Q1-Q2 of FIG. **4A**.

[0069] In FIG. **8A**, a glass substrate of barium borosilicate glass, aluminoborosilicate glass, aluminosilicate glass, or the like available in the market can be used as the substrate **100** having a light-transmitting property. For example, a glass substrate which includes more barium oxide (BaO) than boric acid (B₂O₃) in composition ratio and whose strain point is 730° C. or higher is preferable. This is because the glass substrate is not strained even when the oxide semiconductor layer is thermally processed at high temperatures of about 700° C.

[0070] Next, a conductive layer is formed entirely over the substrate **100**. After that, a resist mask is formed by a first photolithography process, and an unnecessary portion is removed by etching to

form wirings and an electrode (such as a gate wiring including a gate electrode **101**, a capacitor wiring, and a terminal). At this time, the etching is performed so that at least an end portion of the gate electrode **101** is tapered.

[0071] The gate wiring including the gate electrode **101**, the capacitor wiring, and the terminal of a terminal portion are desirably formed from a low-resistance conductive material such as aluminum (Al) or copper (Cu); however, since aluminum itself has disadvantages such as low heat resistance and a tendency to be corroded, it is used in combination with a conductive material having heat resistance. As a conductive material having heat resistance, an element selected from titanium (Ti), tantalum (Ta), tungsten (W), molybdenum (Mo), chromium (Cr), neodymium (Nd), or scandium (Sc), or an alloy including any of the elements, an alloy film including a combination of such elements, or a nitride film including any of the elements can be used.

[0072] Subsequently, a gate insulating layer **102** is formed entirely over the gate electrode **101**. The gate insulating layer **102** is formed by a sputtering method or the like to a thickness of 50 nm to 250 nm.

[0073] For example, a silicon oxide film is formed by a sputtering method to a thickness of 100 nm as the gate insulating layer **102**. Needless to say, the gate insulating layer **102** is not limited to such a silicon oxide film and may be a single layer or a stack of layers including another insulating film, such as a silicon oxynitride film, a silicon nitride film, an aluminum oxide film, or a tantalum oxide film.

[0074] Next, plasma treatment is performed on the gate insulating layer **102** prior to formation of the first oxide semiconductor layer. Here, reverse sputtering where plasma is generated by introduction of an oxygen gas and an argon gas into a deposition chamber is performed, so that the gate insulating layer is subjected to treatment using oxygen radicals or oxygen. Thus, dust adhering to the surface is removed and moreover the surface of the gate insulating layer is modified into an oxygen-excess region. It is effective to perform the oxygen radical treatment on the surface of the gate insulating layer so that the surface is made into an oxygen-excess region, because an oxygen supply source for modifying the interface between the gate insulating layer and the first oxide semiconductor layer is made in thermal treatment (200° C. to 600° C.) for increasing the reliability in a later step.

[0075] The gate insulating layer **102**, the first oxide semiconductor layer, and an insulating film serving as the channel protective layer can be formed by a sputtering method successively without exposure to air by changing the gas introduced to the chamber and the target set in the chamber as appropriate. The successive film formation without exposure to air can prevent impurity mixture. In the case of successive film formation without exposure to air, a manufacturing apparatus of multichamber type is preferable.

[0076] In particular, it is preferable to successively form the gate insulating layer **102** in contact with the first oxide semiconductor layer and the first oxide semiconductor layer. By the successive film formation like this, an interface between stacked layers can be formed without being contaminated by an atmospheric constituent such as moisture or a contaminant impurity element or dust existing in the atmosphere. Thus, variations in characteristics of the non-linear elements and thin film transistors can be reduced.

[0077] Note that the term “successive film formation” in this specification means that during a series of steps of from a first film-formation step by sputtering to a second film-formation step by sputtering, an atmosphere in which a substrate to be processed is disposed is not contaminated by a contaminant atmosphere such as air, and is constantly controlled to be vacuum or an inert gas atmosphere (a nitrogen atmosphere or a rare gas atmosphere). By the successive film formation, film formation can be conducted to a substrate which has been cleaned, without re-attachment of moisture or the like.

[0078] After the plasma treatment to the gate insulating layer **102**, the first oxide semiconductor layer is formed in such a manner that the substrate on which the plasma treatment has been

performed is not exposed to air. The first oxide semiconductor layer formed in such a manner that the substrate on which the plasma treatment has been performed is not exposed to air can avoid the trouble that dust or moisture adheres to the interface between the gate insulating layer and the semiconductor film. Here, the first oxide semiconductor layer is formed in an oxygen atmosphere under the condition where the target is a semiconductor target including In, Ga, and Zn (composition ratio is $\text{In.sub.2O.sub.3:Ga.sub.2O.sub.3:ZnO}=1:1:1$) with a diameter of 8 inches, the distance between the substrate and the target is set at 170 mm, the pressure is set at 0.4 Pa, and the direct current (DC) power supply is set at 0.5 kW. Note that a pulse direct current (DC) power supply is preferable because dust can be reduced and the film thickness can be uniform. The thickness of the first oxide semiconductor layer is set to 5 nm to 200 nm. The thickness of the first oxide semiconductor layer in Embodiment 2 is 100 nm.

[0079] When the first oxide semiconductor layer is formed under the different condition from the second oxide semiconductor layer, the first oxide semiconductor layer has different composition from the second oxide semiconductor layer; for example, the first oxide semiconductor layer includes more oxygen than the second oxide semiconductor layer. In this case, for example, as compared with the oxygen gas flow rate and the argon gas flow rate in the deposition condition of the second oxide semiconductor layer, the oxygen gas flow rate in the deposition condition of the first oxide semiconductor layer is increased. Specifically, the second oxide semiconductor layer is formed in a rare gas (such as argon or helium) atmosphere (or a gas including oxygen at 10% or less and argon at 90% or more), while the first oxide semiconductor layer is formed in an oxygen atmosphere (or a mixed gas of oxygen and argon with the flow rate of oxygen being more than that of argon, and the argon gas flow rate: the oxygen gas flow rate=1:1 or more). When the first oxide semiconductor layer includes more oxygen than the second oxide semiconductor layer, the first oxide semiconductor layer can have lower electrical conductivity than the second oxide semiconductor layer. Moreover, when the first oxide semiconductor layer includes a large amount of oxygen, the amount of off current can be reduced; therefore, a thin film transistor with a high on/off ratio can be provided.

[0080] The first oxide semiconductor layer may be formed in the same chamber as the chamber where the reverse sputtering is performed previously, or may be formed in a different chamber from the chamber where the reverse sputtering is performed previously as long as the film formation can be performed without exposure to air.

[0081] Next, the insulating film serving as the channel protective layer is formed over the first oxide semiconductor layer, following the film formation of the semiconductor film. By successive film formation like this, in a region of the semiconductor film, which is on the side opposite to the side being in contact with the gate insulating film, so-called back channel portion, an interface between stacked layers can be formed without being contaminated by an atmospheric constituent such as moisture or a contaminant impurity element or dust existing in the atmosphere. Thus, variations in characteristics of the non-linear elements can be reduced.

[0082] A multichamber sputtering apparatus in which a silicon oxide (artificial quartz) target and a target for an oxide semiconductor film are provided is used to form a silicon oxide film as the channel protective layer, without the first oxide semiconductor layer formed in the previous step, being exposed to air.

[0083] Next, with use of a resist mask formed using a second photomask in Embodiment 2, the silicon oxide film formed over the first oxide semiconductor layer is selectively etched to form a channel protective layer **133**.

[0084] Next, a second oxide semiconductor layer is formed over the channel protective layer **133** and the first oxide semiconductor layer by a sputtering method. Here, sputtering deposition is performed under the condition where a 8-inch-diameter target includes indium oxide (In.sub.2O.sub.3), gallium oxide (Ga.sub.2O.sub.3), and zinc oxide (ZnO) at a composition ratio of 1:1:1 ($=\text{In.sub.2O.sub.3:Ga.sub.2O.sub.3:ZnO}$), the distance between the target and the substrate is

170 nm, the pressure in a deposition chamber is set at 0.4 Pa, the DC electric power is set at 0.5 kW, the deposition temperature is set to room temperature, and the argon gas flow rate is set at 40 sccm. Thus, a semiconductor film including In, Ga, Zn, and oxygen as components is formed as the second oxide semiconductor layer. Although the target where the composition ratio is $\text{In.sub.2O.sub.3:Ga.sub.2O.sub.3:ZnO}=1:1:1$ is used intentionally, an oxide semiconductor film including a crystal grain which has a size of 1 nm to 10 nm just after the film formation is often obtained. It can be said that the presence or absence of crystal grains and the density of crystal grains can be controlled and the diameter of the crystal grain can be adjusted within 1 nm to 10 nm, by adjusting as appropriate, the deposition condition of reactive sputtering, such as the target composition ratio, the deposition pressure (0.1 Pa to 2.0 Pa), the electric power (250 W to 3000 W: 8 inches ϕ), the temperature (room temperature to 100° C.), and the like. The thickness of the second oxide semiconductor layer is set to 5 nm to 20 nm. Needless to say, in the case where the film includes crystal grains, the size of the crystal grain does not exceed the film thickness. In Embodiment 2, the second oxide semiconductor layer has a thickness of 5 nm.

[0085] Next, a third photolithography process is performed to form a resist mask, and the first oxide semiconductor layer and the second oxide semiconductor layer are etched. Here, wet etching is performed using ITO07N (product of Kanto Chemical Co., Inc.) to remove an unnecessary portion; thus, a first oxide semiconductor layer **103** and a second oxide semiconductor layer **111** are formed. Note that the etching here may be dry etching, without being limited to wet etching. The cross-section at this phase is illustrated in FIG. 8B.

[0086] Next, a conductive film **132** is formed from a metal material over the second oxide semiconductor layer **111** and the gate insulating layer **102** by a sputtering method or a vacuum evaporation method. As the material of the conductive film **132**, there are an element selected from Al, Cr, Ta, Ti, Mo, and W, an alloy including the above element, an alloy film in which some of the above elements are combined, and the like.

[0087] When heat treatment is conducted at 200° C. to 600° C., the conductive film preferably has heat resistant property so as to endure this heat treatment. Since aluminum itself has disadvantages such as low heat resistance and a tendency to be corroded, it is used in combination with a conductive material having heat resistance. As a conductive material having heat resistance, which can be used in combination with Al, an element selected from titanium (Ti), tantalum (Ta), tungsten (W), molybdenum (Mo), chromium (Cr), neodymium (Nd), or scandium (Sc), or an alloy including any of the elements, an alloy film including a combination of such elements, or a nitride film including any of the elements can be used.

[0088] In this embodiment, the conductive film **132** has a three-layer structure in which a Ti film is formed, an aluminum film including Nd (Al—Nd) is stacked over the Ti film, and another Ti film is stacked thereover. Alternatively, the conductive film **132** may have a two-layer structure in which a Ti film is stacked over an Al film. Further alternatively, the conductive film **132** may have a single-layer structure of an aluminum film including silicon or a titanium film. The cross section at this phase is illustrated in FIG. 8C.

[0089] Next, a fourth photolithography process is performed to form a resist mask **131**, and an unnecessary part of the conductive film **132** is removed by etching. Thus, conductive layers **105a** and **105b** are formed (FIG. 9A). At this time, dry etching or wet etching can be used as the etching. In Embodiment 2, dry etching is employed using a mixed gas of SiCl.sub.4 , Cl.sub.2 , and BCl.sub.3 to etch the conductive film in which the Ti film, the aluminum film including Nd (Al—Nd) and the Ti film are stacked. In this manner, the conductive layers **105a** and **105b** are formed.

[0090] Next, the second oxide semiconductor layer exposed between the conductive layer **105a** and the conductive layer **105b** is etched using the same mask as that used for the etching the conductive film **132**. Here, wet etching is performed using ITO07N (product of Kanto Chemical Co., Inc.) to remove an unnecessary portion; thus, second oxide semiconductor layers (**104a** and **104b**) are formed. Note that the etching here may be dry etching, without being limited to wet etching. In

addition, the first oxide semiconductor layer and the second oxide semiconductor layer are dissolved in the same etchant. Accordingly, when the second oxide semiconductor layer is directly formed on the first oxide semiconductor layer, it is difficult to etch only the second oxide semiconductor layer selectively. However, in Embodiment 2, the second oxide semiconductor layer is formed over the first oxide semiconductor layer with the channel protective layer **133** therebetween, and thereby there is no possibility that the first oxide semiconductor layer **103** is damaged in etching the second oxide semiconductor layer.

[0091] Next, thermal treatment at 200° C. to 600° C., typically 300° C. to 500° C., is preferably performed. In this case, thermal treatment is performed in a furnace at 350° C. for an hour in a nitrogen atmosphere. This thermal treatment allows atoms of the semiconductor layers including In, Ga, and Zn to be rearranged. Since the distortion that interrupts carrier movement is released by this thermal treatment, the thermal treatment at this time (including photo-annealing) is important. There is no particular limitation on when to perform the thermal treatment as long as it is performed after the formation of the first oxide semiconductor layer; for example, it is performed after the formation of the protective film. Through these steps, the non-linear element **170a** in which the first oxide semiconductor layer **103** is a channel formation region is completed. A cross-sectional view at this phase is illustrated in FIG. 9A.

[0092] Next, the resist mask is removed, and a protective insulating film **107** covering the non-linear element **170a** is formed. The protective insulating film **107** can be formed using a silicon nitride film, a silicon oxide film, a silicon oxynitride film, an aluminum oxide film, a tantalum oxide film, or the like by a sputtering method or the like.

[0093] Next, a fifth photolithography process is performed to form a resist mask, and the protective insulating film **107** is etched. Thus, a contact hole **125** that reaches the conductive layer **105b** is formed. In order to reduce the number of masks used, it is preferable to etch the gate insulating layer **102** by using the same resist mask so as to form a contact hole **128** that reaches the gate electrode. A cross-sectional view at this phase is illustrated in FIG. 9B.

[0094] Then, the resist mask is removed, and then a transparent conductive film is formed. As a material for the transparent conductive film, indium oxide (In.sub.2O.sub.3), indium oxide-tin oxide alloy (In.sub.2O.sub.3—SnO.sub.2, abbreviated to ITO), or the like can be given, and it can be formed by a sputtering method, a vacuum evaporation method, or the like. Etching treatment of such materials is performed using a chlorinated acid based solution. However, since etching of ITO particularly tends to leave residue, an alloy of indium oxide and zinc oxide (In.sub.2O.sub.3—ZnO) may be used in order to improve etching processability.

[0095] Next, a sixth photolithography process is performed to form a resist mask, and an unnecessary portion of the transparent conductive film is removed. Thus, a pixel electrode is formed, which is not illustrated.

[0096] Moreover, in this sixth photolithography process, a capacitor wiring and the pixel electrode together form a storage capacitor in a capacitor portion, which is not illustrated, by using the gate insulating layer **102** and the protective insulating film **107** as dielectrics.

[0097] Moreover, in this sixth photolithography process, the resist mask covers a terminal portion, so that the transparent conductive film formed in the terminal portion is left. The transparent conductive film serves as an electrode or a wiring used for connection with an FPC, a terminal electrode for connection which functions as an input terminal of a source wiring, or the like.

[0098] Moreover, in Embodiment 2, the conductive layer **105b** serving as a drain electrode layer of the non-linear element **170a** is connected to the scan line **108** in the contact holes **125** and **128** via the third wiring layer **110** formed using the transparent conductive film, and thereby the protective circuit is formed.

[0099] Then, the resist mask is removed. A cross-sectional view at this phase is illustrated in FIG. 9C.

[0100] Through the six photolithography processes performed in the above manner, the protective

circuit having the plurality of non-linear elements (in Embodiment 2, the two non-linear elements **170a** and **170b**) can be completed by using the six photomasks. In the connection structure between the first oxide semiconductor layer of the non-linear element and the wiring layers, the provision of the region which is bonded with the second oxide semiconductor layer, which has higher electrical conductivity than the first oxide semiconductor layer, allows stable operation as compared with a case of using only metal wirings. According to Embodiment 2, a plurality of TFTs can be completed together with the non-linear elements by a similar method to that of the non-linear elements. Therefore, a pixel portion including bottom-gate n-channel TFTs and a protective circuit can be manufactured at the same time. In other words, a board for an active matrix display device, on which a protective diode which has fewer defects due to film peeling, is mounted, can be manufactured in accordance with the steps described in Embodiment 2.

[0101] In addition, if the first oxide semiconductor layer **103** is damaged, electric characteristics of the non-linear element also becomes worse. However, because the channel formation region in the first oxide semiconductor layer of the non-linear element in Embodiment 2 is protected by the channel protective layer, there is no possibility that the first oxide semiconductor layer **103** is damaged in the etching step of the conductive film **132** serving as a source electrode and a drain electrode and in the etching step of the second oxide semiconductor layer. Therefore, the non-linear element of Embodiment 2, in which the channel formation region is protected by the channel protective layer, has high reliability, and a display device including a protective circuit using the non-linear element also has high reliability.

Embodiment 3

[0102] In Embodiment 3, an example of a display device including a pixel portion and a protective circuit including a non-linear element provided around the pixel portion, which is different from that of Embodiment 2, will now be described with reference to FIGS. **27A** and **27B**.

[0103] FIG. **27A** is a cross-sectional view of a display device in which a thin film transistor arranged in a pixel portion and a protective circuit including a non-linear element are formed over the same substrate. In a non-linear element **270a**, conductive layers (**105a** and **105b**) serving as a source electrode and a drain electrode are provided in contact with the first oxide semiconductor layer **103**.

[0104] In the non-linear element **270a**, the conductive layer **105a** and the conductive layer **105b** are preferably in contact with the first oxide semiconductor layer **103** which is modified by plasma treatment. In Embodiment 3, the first oxide semiconductor layer **103** is subjected to plasma treatment before formation of the conductive layers.

[0105] As the plasma treatment, for example, reverse sputtering can be conducted. The plasma treatment can be conducted by using an argon gas, a hydrogen gas, or a mixed gas of argon and hydrogen. Further, an oxygen gas may be contained in such a gas. Alternatively, another rare gas may be used, instead of the argon gas.

[0106] As illustrated in FIG. **27B**, a protective insulating film **107** and an insulating layer **136** may be formed over the first oxide semiconductor layer **103**, as an interlayer insulating layer. The conductive layer **105a** and the conductive layer **105b** are in contact with and electrically connected to the first oxide semiconductor layer **103**, through contact holes formed in the protective insulating film **107** and the insulating layer **136**.

[0107] In FIG. **27B**, the gate insulating layer **102** and the channel protective layer **133** are formed using silicon oxide layers; the first oxide semiconductor layer **103**, an oxide semiconductor layer including In, Ga, and Zn, which is in oxygen-excess state; and the insulating layer **135**, a silicon nitride layer, by a sputtering method.

[0108] Also in FIG. **27B**, plasma treatment is preferably conducted to the first oxide semiconductor layer **103** prior to the formation of the conductive layers (**105a** and **105b**) serving as a source electrode and a drain electrode. The plasma treatment may be conducted after the channel protective layer **133** is formed over the first oxide semiconductor layer **103**, or to the first oxide

semiconductor layer **103** exposed in the bottom of the contact holes formed in the protective insulating film **107** and the insulating layer **136**.

[0109] By formation of the conductive layers (**105a** and **105b**) serving as a source electrode and a drain electrode in contact with the first oxide semiconductor layer **103** modified by the plasma treatment, contact resistance between the first oxide semiconductor layer **103** and the conductive layers (**105a** and **105b**) serving as a source electrode and a drain electrode can be reduced. In addition, the bonding strength between the first oxide semiconductor layer **103** and the conductive layers (**105a** and **105b**) serving as a source electrode and a drain electrode is improved by the plasma treatment, and thereby defects due to film peeling hardly occurs.

[0110] Through the above-described steps, a display device having a highly reliable protective circuit as a non-linear semiconductor device can be manufactured.

[0111] In addition, if the first oxide semiconductor layer **103** is damaged, electric characteristics of the non-linear element also becomes worse. However, because the channel formation region in the first oxide semiconductor layer of the non-linear element in Embodiment 3 is protected by the channel protective layer, there is no possibility that the first oxide semiconductor layer **103** is damaged in the etching step of the conductive layer serving as a source electrode and a drain electrode. Therefore, the non-linear element of Embodiment 3, in which the channel formation region is protected by the channel protective layer, has high reliability, and a display device including a protective circuit using the non-linear element also has high reliability.

[0112] Embodiment 3 can be implemented in combination with any structure of the other embodiments as appropriate.

Embodiment 4

[0113] Embodiment 4 illustrates an example of electronic paper in which a protective circuit and a TFT in a pixel portion are provided over one substrate, as a display device according to one embodiment of the present invention.

[0114] FIG. **10** illustrates active matrix type electronic paper device as an example of a display device according to one embodiment of the present invention. A thin film transistor **581** used for a semiconductor device can be manufactured in a manner similar to the non-linear element described in Embodiment 2, and has high electrical characteristics, in which an oxide semiconductor including In, Ga and Zn is used for a semiconductor layer and a source region and a drain region.

[0115] The electronic paper in FIG. **10** is an example of a display device in which a twisting ball display system is employed. The twisting ball display system refers to a method in which spherical particles each colored in black and white are arranged between a first electrode layer and a second electrode layer which are electrode layers used for a display element, and a potential difference is generated between the first electrode layer and the second electrode layer to control orientation of the spherical particles, so that display is performed.

[0116] The thin film transistor **581** has a bottom-gate structure in which the source electrode layer or the drain electrode layer is electrically connected to a first electrode layer **587** in an opening formed in an insulating layer **585**. A gate insulating layer **583** is over a gate electrode, and a protective layer **584** is over a channel protective layer. Between the first electrode layer **587** and a second electrode layer **588**, spherical particles **589** are provided. Each spherical particle **589** includes a black region **590a** and a white region **590b**, and a cavity **594** filled with liquid around the black region **590a** and the white region **590b**. The circumference of the spherical particle **589** is filled with filler **595** such as a resin or the like. These are between a first substrate and a second substrate (see FIG. **10**).

[0117] Further, instead of the twisting ball, an electrophoretic element can be used. A microcapsule having a diameter of about 10 μm to 20 μm , which is filled with transparent liquid, positively-charged white microparticles and negatively-charged black microparticles, is used. In the microcapsule which is provided between the first electrode layer and the second electrode layer, when an electric field is applied by the first electrode layer and the second electrode layer, the

white microparticles and the black microparticles move to opposite sides to each other, so that white or black can be displayed. A display element using this principle is an electrophoretic display element, and is called electronic paper in general. The electrophoretic display element has higher reflectance than a liquid crystal display element, and thus, an assistant light is unnecessary. Moreover, power consumption is low and a display portion can be recognized in a dusky place. Furthermore, an image which is displayed once can be retained even when power is not supplied to the display portion. Accordingly, a displayed image can be stored even though a semiconductor device having a display function (which is also referred to simply as a display device or a semiconductor device provided with a display device) is distanced from an electric wave source which serves as a power supply.

[0118] Through the above steps, in the connection structure between the first oxide semiconductor layer of the non-linear element and the wiring layers, the provision of the region which is bonded with the second oxide semiconductor layer, which has higher electrical conductivity than the first oxide semiconductor layer, allows stable operation as compared with a case of using only metal wirings. Accordingly, the function of the protective circuit is enhanced and the operation can be made stable. Moreover, it is possible to manufacture a highly-reliable electronic paper device having stable operation, by incorporating a protective circuit including the non-linear elements in which defects due to the peeling of the thin films are not easily caused.

[0119] In addition, if the first oxide semiconductor layer is damaged, electric characteristics of the non-linear element also becomes worse. However, because the channel formation region in the first oxide semiconductor layer of the non-linear element in Embodiment 4 is protected by the channel protective layer, there is no possibility that the first oxide semiconductor layer is damaged in the etching step of the conductive film serving as a source electrode and a drain electrode and in the etching step of the second oxide semiconductor layer. Therefore, the non-linear element of Embodiment 4, in which the channel formation region is protected by the channel protective layer, has high reliability, and electronic paper including a protective circuit using the non-linear element also has high reliability.

[0120] Embodiment 4 can be implemented in combination with any structure of the other embodiments as appropriate.

Embodiment 5

[0121] Embodiment 5 describes an example of manufacturing at least a protective circuit, part of a driver circuit, and a thin film transistor of a pixel portion over one substrate in a display device which is an example of a semiconductor device according to one embodiment of the present invention, with reference to FIGS. 11A and 11B, FIG. 12, FIG. 13, FIG. 14, FIG. 15 and FIG. 16.

[0122] The thin film transistor in the pixel portion formed over the same substrate as the protective circuit is formed in a manner similar to the non-linear element described in Embodiment 2 or 3. The thin film transistor is formed to be an n-channel TFT; therefore, part of a driver circuit which can be formed using an n-channel TFT is formed over the same substrate as the thin film transistor in the pixel portion.

[0123] FIG. 11A illustrates an example of a block diagram of an active matrix liquid crystal display device which is an example of a semiconductor device according to one embodiment of the present invention. The display device illustrated in FIG. 11A includes over a substrate 5300, a pixel portion 5301 including a plurality of pixels each provided with a display element; a scan line driver circuit 5302 that selects a pixel; and a signal line driver circuit 5303 that controls a video signal input to a selected pixel.

[0124] The pixel portion 5301 is connected to the signal line driver circuit 5303 with a plurality of signal lines S1 to Sm (not illustrated) extending in a column direction from the signal line driver circuit 5303 and connected to the scan line driver circuit 5302 with a plurality of scan lines G1 to Gn (not illustrated) extending in a row direction from the scan line driver circuit 5302. The pixel portion 5301 includes a plurality of pixels (not illustrated) arranged in matrix, corresponding to the

signal lines **S1** to **Sm** and the scan lines **G1** to **Gn**. In addition, each of the pixels is connected to a signal line **Sj** (any one of the signal lines **S1** to **Sm**) and a scan line **Gi** (any one of the scan lines **G1** to **Gn**).

[0125] The thin film transistor that can be formed together with non-linear element described in Embodiment 2 or 3 by a method similar to that of the non-linear element described in Embodiment 2 or 3 is an n-channel TFT, and a signal line driver circuit including an n-channel TFT is described with reference to FIG. 12.

[0126] The signal line driver circuit in FIG. 12 includes a driver IC **5601**, switch groups **5602_1** to **5602_M**, a first wiring **5611**, a second wiring **5612**, a third wiring **5613**, and wirings **5621_1** to **5621_M**. Each of the switch groups **5602_1** to **5602_M** includes a first thin film transistor **5603a**, a second thin film transistor **5603b**, and a third thin film transistor **5603c**.

[0127] The driver IC **5601** is connected to the first wiring **5611**, the second wiring **5612**, the third wiring **5613**, and the wirings **5621_1** to **5621_M**. Each of the switch groups **5602_1** to **5602_M** is connected to the first wiring **5611**, the second wiring **5612**, the third wiring **5613**, and one of the wirings **5621_1** to **5621_M** corresponding to the switch groups **5602_1** to **5602_M**, respectively. Each of the wirings **5621_1** to **5621_M** is connected to three signal lines through the first thin film transistor **5603a**, the second thin film transistor **5603b**, and the third thin film transistor **5603c**. For example, the wiring **5621_J** of the J-th column (one of the wirings **5621_1** to **5621_M**) is connected to a signal line **Sj-1**, a signal line **Sj**, and a signal line **Sj+1** through the first thin film transistor **5603a**, the second thin film transistor **5603b**, and the third thin film transistor **5603c** of the switch group **5602_J**.

[0128] Note that a signal is input to each of the first wiring **5611**, the second wiring **5612**, and the third wiring **5613**.

[0129] Note that the driver IC **5601** is preferably formed on a single-crystal substrate. The switch groups **5602_1** to **5602_M** are preferably formed over the same substrate as the pixel portion. Therefore, the driver IC **5601** may be connected to the switch groups **5602_1** to **5602_M** through an FPC or the like.

[0130] Next, operation of the signal line driver circuit in FIG. 12 is described with reference to a timing chart of FIG. 13. FIG. 13 illustrates the timing chart where a scan line **Gi** in the i-th row is selected. A selection period of the scan line **Gi** in the i-th row is divided into a first sub-selection period **T1**, a second sub-selection period **T2**, and a third sub-selection period **T3**. In addition, the signal line driver circuit in FIG. 12 operates similarly to FIG. 13 also when a scan line of another row is selected.

[0131] Note that the timing chart in FIG. 13 illustrates a case where the wiring **5621_J** in the J-th column is connected to the signal line **Sj-1**, the signal line **Sj**, and the signal line **Sj+1** through the first thin film transistor **5603a**, the second thin film transistor **5603b**, and the third thin film transistor **5603c**.

[0132] The timing chart of FIG. 13 illustrates timing when the scan line **Gi** in the i-th row is selected, timing **5703a** when the first thin film transistor **5603a** is turned on/off, timing **5703b** when the second thin film transistor **5603b** is turned on/off, timing **5703c** when the third thin film transistor **5603c** is turned on/off, and a signal **5721_J** input to the wiring **5621_J** in the J-th column.

[0133] In the first sub-selection period **T1**, the second sub-selection period **T2**, and the third sub-selection period **T3**, different video signals are input to the wirings **5621_1** to **5621_M**. For example, a video signal input to the wiring **5621_J** in the first sub-selection period **T1** is input to the signal line **Sj-1**, a video signal input to the wiring **5621_J** in the second sub-selection period **T2** is input to the signal line **Sj**, and a video signal input to the wiring **5621_J** in the third sub-selection period **T3** is input to the signal line **Sj+1**. In addition, in the first sub-selection period **T1**, the second sub-selection period **T2**, and the third sub-selection period **T3**, the video signals input to the wiring **5621_J** are denoted by **Data_j-1**, **Data_j**, and **Data_j+1**.

[0134] As illustrated in FIG. 13, in the first sub-selection period **T1**, the first thin film transistor

5603a is turned on, and the second thin film transistor **5603b** and the third thin film transistor **5603c** are turned off. At this time, Data_{j-1} input to the wiring **5621_J** is input to the signal line S_{j-1} via the first thin film transistor **5603a**. In the second sub-selection period T2, the second thin film transistor **5603b** is turned on, and the first thin film transistor **5603a** and the third thin film transistor **5603c** are turned off. At this time, Data_j input to the wiring **5621_J** is input to the signal line S_j via the second thin film transistor **5603b**. In the third sub-selection period T3, the third thin film transistor **5603c** is turned on, and the first thin film transistor **5603a** and the second thin film transistor **5603b** are turned off. At this time, Data_{j+1} input to the wiring **5621_J** is input to the signal line S_{j+1} via the third thin film transistor **5603c**.

[0135] As described above, in the signal line driver circuit in FIG. 12, by dividing one gate selection period into three, video signals can be input to three signal lines from one wiring **5621** in one gate selection period. Therefore, in the signal line driver circuit in FIG. 12, the number of connections of the substrate provided with the driver IC **5601** and the substrate provided with the pixel portion can be approximately $\frac{1}{3}$ of the number of signal lines. The number of connections is reduced to approximately $\frac{1}{3}$ of the number of the signal lines, so that reliability, yield, etc., of the signal line driver circuit in FIG. 12 can be improved.

[0136] Note that there are no particular limitations on the arrangement, the number, a driving method, and the like of the thin film transistors, as long as one gate selection period is divided into a plurality of sub-selection periods and video signals are input to a plurality of signal lines from one wiring in the respective the sub-selection periods as illustrated in FIG. 12.

[0137] For example, when video signals are input to three or more signal lines from one wiring in each of three or more sub-selection periods, it is only necessary to add a thin film transistor and a wiring for controlling the thin film transistor. Note that when one gate selection period is divided into four or more sub-selection periods, one sub-selection period becomes shorter. Therefore, one gate selection period is preferably divided into two or three sub-selection periods.

[0138] As another example, one gate selection period may be divided into a precharge period T_p, the first sub-selection period T1, the second sub-selection period T2, and the third sub-selection period T3 as illustrated in a timing chart in FIG. 14. The timing chart in FIG. 14 illustrates timing at which the scan line G_i of the i-th row is selected, timing **5803a** of on/off of the first thin film transistor **5603a**, timing **5803b** of on/off of the second thin film transistor **5603b**, timing **5803c** of on/off of the third thin film transistor **5603c**, and a signal **5821_J** input to the wiring **5621_J** of the J-th column. As illustrated in FIG. 14, the first thin film transistor **5603a**, the second thin film transistor **5603b**, and the third thin film transistor **5603c** are turned on in the precharge period T_p. At this time, precharge voltage V_p input to the wiring **5621_J** is input to each of the signal line S_{j-1}, the signal line S_j, and the signal line S_{j+1} via the first thin film transistor **5603a**, the second thin film transistor **5603b**, and the third thin film transistor **5603c**. In the first sub-selection period T1, the first thin film transistor **5603a** is turned on, and the second thin film transistor **5603b** and the third thin film transistor **5603c** are turned off. At this time, Data_{j-1} input to the wiring **5621_J** is input to the signal line S_{j-1} via the first thin film transistor **5603a**. In the second sub-selection period T2, the second thin film transistor **5603b** is turned on, and the first thin film transistor **5603a** and the third thin film transistor **5603c** are turned off. At this time, Data_j input to the wiring **5621_J** is input to the signal line S_j via the second thin film transistor **5603b**. In the third sub-selection period T3, the third thin film transistor **5603c** is turned on, and the first thin film transistor **5603a** and the second thin film transistor **5603b** are turned off. At this time, Data_{j+1} input to the wiring **5621_J** is input to the signal line S_{j+1} via the third thin film transistor **5603c**.

[0139] As described above, in the signal line driver circuit in FIG. 12 to which the timing chart in FIG. 14 is applied, the video signal can be written to the pixel at high speed because the signal line can be precharged by providing a precharge selection period before a sub-selection period. Note that portions in FIG. 14 which are similar to those of FIG. 13 are denoted by common reference numerals and detailed description of the portions which are the same and portions which have

similar functions is omitted.

[0140] Further, a structure of a scan line driver circuit is described. The scan line driver circuit includes a shift register and a buffer. Additionally, the scan line driver circuit may include a level shifter in some cases. In the scan line driver circuit, when the clock signal (CLK) and the start pulse signal (SP) are input to the shift register, a selection signal is produced. The generated selection signal is buffered and amplified by the buffer, and the resulting signal is supplied to a corresponding scan line. Gate electrodes of transistors in pixels of one line are connected to the scan line. Further, since the transistors in the pixels of one line have to be turned on at the same time, a buffer which can feed a large current can be used.

[0141] One mode of a shift register which is used for a part of a scan line driver circuit is described with reference to FIG. 15 and FIG. 16.

[0142] FIG. 15 illustrates a circuit configuration of the shift register. The shift register illustrated in FIG. 15 includes a plurality of flip-flops (flip-flops 5701-1 to 5701-n). The shift register is operated with input of a first clock signal, a second clock signal, a start pulse signal, and a reset signal.

[0143] Connection relations of the shift register in FIG. 15 are described. In the i-th stage flip-flop 5701_i (one of the flip-flops 5701-1 to 5701_n) in the shift register of FIG. 15, a first wiring 5501 illustrated in FIG. 16 is connected to a seventh wiring 5717_i-1; a second wiring 5502 illustrated in FIG. 16 is connected to a seventh wiring 5717_i+1; a third wiring 5503 illustrated in FIG. 16 is connected to a seventh wiring 5717_i; and a sixth wiring 5506 illustrated in FIG. 16 is connected to a fifth wiring 5715.

[0144] Further, a fourth wiring 5504 illustrated in FIG. 16 is connected to a second wiring 5712 in flip-flops of odd-numbered stages, and is connected to a third wiring 5713 in flip-flops of even-numbered stages. A fifth wiring 5505 illustrated in FIG. 16 is connected to a fourth wiring 5714.

[0145] Note that the first wiring 5501 of the first stage flip-flop 5701_1 illustrated in FIG. 16 is connected to a first wiring 5711. Moreover, the second wiring 5502 of the n-th stage flip-flop 5701_n illustrated in FIG. 16 is connected to a sixth wiring 5716.

[0146] Note that the first wiring 5711, the second wiring 5712, the third wiring 5713, and the sixth wiring 5716 may be referred to as a first signal line, a second signal line, a third signal line, and a fourth signal line, respectively. The fourth wiring 5714 and the fifth wiring 5715 may be referred to as a first power source line and a second power source line, respectively.

[0147] Next, FIG. 16 illustrates details of the flip-flop illustrated in FIG. 15. A flip-flop illustrated in FIG. 16 includes a first thin film transistor 5571, a second thin film transistor 5572, a third thin film transistor 5573, a fourth thin film transistor 5574, a fifth thin film transistor 5575, a sixth thin film transistor 5576, a seventh thin film transistor 5577, and an eighth thin film transistor 5578. Each of the first thin film transistor 5571, the second thin film transistor 5572, the third thin film transistor 5573, the fourth thin film transistor 5574, the fifth thin film transistor 5575, the sixth thin film transistor 5576, the seventh thin film transistor 5577, and the eighth thin film transistor 5578 is an n-channel transistor and is turned on when the gate-source voltage (Vgs) exceeds the threshold voltage (Vth).

[0148] Next, the connection structure of the flip-flop illustrated in FIG. 16 is described below.

[0149] A first electrode (one of a source electrode and a drain electrode) of the first thin film transistor 5571 is connected to the fourth wiring 5504. A second electrode (the other of the source electrode and the drain electrode) of the first thin film transistor 5571 is connected to the third wiring 5503.

[0150] A first electrode of the second thin film transistor 5572 is connected to the sixth wiring 5506. A second electrode of the second thin film transistor 5572 is connected to the third wiring 5503.

[0151] A first electrode of the third thin film transistor 5573 is connected to the fifth wiring 5505. A second electrode of the third thin film transistor 5573 is connected to a gate electrode of the second thin film transistor 5572. A gate electrode of the third thin film transistor 5573 is connected to the

fifth wiring **5505**.

[0152] A first electrode of the fourth thin film transistor **5574** is connected to the sixth wiring **5506**. A second electrode of the fourth thin film transistor **5574** is connected to the gate electrode of the second thin film transistor **5572**. A gate electrode of the fourth thin film transistor **5574** is connected to a gate electrode of the first thin film transistor **5571**.

[0153] A first electrode of the fifth thin film transistor **5575** is connected to the fifth wiring **5505**. A second electrode of the fifth thin film transistor **5575** is connected to the gate electrode of the first thin film transistor **5571**. A gate electrode of the fifth thin film transistor **5575** is connected to the first wiring **5501**.

[0154] A first electrode of the sixth thin film transistor **5576** is connected to the sixth wiring **5506**. A second electrode of the sixth thin film transistor **5576** is connected to the gate electrode of the first thin film transistor **5571**. A gate electrode of the sixth thin film transistor **5576** is connected to the gate electrode of the second thin film transistor **5572**.

[0155] A first electrode of the seventh thin film transistor **5577** is connected to the sixth wiring **5506**. A second electrode of the seventh thin film transistor **5577** is connected to the gate electrode of the first thin film transistor **5571**. A gate electrode of the seventh thin film transistor **5577** is connected to the second wiring **5502**. A first electrode of the eighth thin film transistor **5578** is connected to the sixth wiring **5506**. A second electrode of the eighth thin film transistor **5578** is connected to the gate electrode of the second thin film transistor **5572**. A gate electrode of the eighth thin film transistor **5578** is connected to the first wiring **5501**.

[0156] Note that the points at which the gate electrode of the first thin film transistor **5571**, the gate electrode of the fourth thin film transistor **5574**, the second electrode of the fifth thin film transistor **5575**, the second electrode of the sixth thin film transistor **5576**, and the second electrode of the seventh thin film transistor **5577** are connected are each referred to as a node **5543**. The points at which the gate electrode of the second thin film transistor **5572**, the second electrode of the third thin film transistor **5573**, the second electrode of the fourth thin film transistor **5574**, the gate electrode of the sixth thin film transistor **5576**, and the second electrode of the eighth thin film transistor **5578** are connected are each referred to as a node **5544**.

[0157] Note that the first wiring **5501**, the second wiring **5502**, the third wiring **5503**, and the fourth wiring **5504** may be referred to as a first signal line, a second signal line, a third signal line, and a fourth signal line, respectively. The fifth wiring **5505** and the sixth wiring **5506** may be referred to as a first power source line and a second power source line, respectively.

[0158] Alternatively, the signal line driver circuit and the scan line driver circuit can be manufactured using only n-channel TFTs, which can be manufactured together with a non-linear element by a method similar to the method for manufacturing the non-linear element described in Embodiment 2 or 3. Since the n-channel TFTs which can be formed together with a non-linear element by the method similar to the method for manufacturing the non-linear element described in Embodiment 2 or 3 have high mobility, the driving frequency of the driver circuits can be increased. Further, the n-channel TFTs which can be formed together with a non-linear element by the method similar to the method for manufacturing the non-linear element described in Embodiment 2 or 3 include source regions or drain regions which are formed using an oxygen-deficiency oxide semiconductor layer including indium, gallium, and zinc. Therefore, the parasitic capacitance is decreased and the frequency characteristic (called f-characteristic) is increased. For example, the scan line driver circuit including the n-channel TFTs which can be formed together with a non-linear element by the method similar to the method for manufacturing the non-linear element described in Embodiment 2 or 3 can operate at high speed; therefore, it is possible to increase the frame frequency or to achieve insertion of a black screen, for example.

[0159] In addition, when the channel width of the transistor in the scan line driver circuit is increased or a plurality of scan line driver circuits is provided, for example, higher frame frequency can be realized. When a plurality of scan line driver circuits are provided, a scan line driver circuit

for driving even-numbered scan lines is provided on one side and a scan line driver circuit for driving odd-numbered scan lines is provided on the opposite side; thus, increase in frame frequency can be realized.

[0160] In the case of manufacturing an active matrix type light-emitting display device, which is an example of a semiconductor device according to one embodiment of the present invention, a plurality of scan line driver circuits are preferably arranged because a plurality of thin film transistors are arranged in at least one pixel. An example of a block diagram of an active matrix light-emitting display device is illustrated in FIG. **11B**.

[0161] The light-emitting display device illustrated in FIG. **11B** includes, over a substrate **5400**, a pixel portion **5401** including a plurality of pixels each provided with a display element; a first scan line driver circuit **5402** and a second scan line driver circuit **5404** that select each pixel; and a signal line driver circuit **5403** that controls a video signal input to a selected pixel.

[0162] In the case of inputting a digital video signal to the pixel of the light-emitting display device of FIG. **11B**, the pixel is put in a light-emitting state or non-light-emitting state by switching on/off of the transistor. Thus, grayscale can be displayed using an area ratio grayscale method or a time ratio grayscale method. An area ratio grayscale method refers to a driving method by which one pixel is divided into a plurality of subpixels and the respective subpixels are driven separately based on video signals so that grayscale is displayed. Further, a time ratio grayscale method refers to a driving method by which a period during which a pixel is in a light-emitting state is controlled so that grayscale is displayed.

[0163] Since the response time of light-emitting elements is shorter than that of liquid crystal elements or the like, the light-emitting elements are suitable for a time ratio grayscale method. Specifically, in the case of displaying by a time grayscale method, one frame period is divided into a plurality of subframe periods. Then, in response to video signals, the light-emitting element in the pixel is put in a light-emitting state or a non-light-emitting state in each subframe period. By dividing a frame into a plurality of subframes, the total length of time in which pixels actually emit light in one frame period can be controlled with video signals to display grayscales.

[0164] Note that in the light-emitting display device of FIG. **11B**, in a case where one pixel includes two TFTs, that is, a switching TFT and a current control TFT, a signal which is input to a first scan line serving as a gate wiring of the switching TFT is generated from the first scan line driver circuit **5402** and a signal which is input to a second scan line serving as a gate wiring of the current control TFT is generated from the second scan line driver circuit **5404**. However, the signal which is input to the first scan line and the signal which is input to the second scan line may be generated together from one scan line driver circuit. In addition, for example, there is a possibility that a plurality of the first scan lines used for controlling the operation of the switching element be provided in each pixel depending on the number of transistors included in the switching element. In this case, the signals which are input to the first scan lines may be generated all from one scan line driver circuit or may be generated from a plurality of scan line driver circuits.

[0165] Even in the light-emitting display device, part of the driver circuit which can be formed using the n-channel TFTs can be provided over one substrate together with the thin film transistors of the pixel portion. Moreover, the signal line driver circuit and the scan line driver circuit can be manufactured using only the n-channel TFTs which can be formed together with a non-linear element by a method similar to the method for manufacturing the non-linear element described in Embodiment 2 or 3.

[0166] The aforementioned driver circuit may be used for not only a liquid crystal display device or a light-emitting display device but also electronic paper in which electronic ink is driven by utilizing an element electrically connected to a switching element. The electronic paper is also called an electrophoretic display device (electrophoretic display) and has advantages in that it has the same level of readability as regular paper, it has less power consumption than other display devices, and it can be set to have a thin and light form.

[0167] Electrophoretic displays can have various modes. Electrophoretic displays contain a plurality of microcapsules dispersed in a solvent or a solute, each microcapsule containing first particles which are positive-charged and second particles which are negative-charged. By applying an electric field to the microcapsules, the particles in the microcapsules are moved in opposite directions and only the color of the particles concentrated on one side is exhibited. It is to be noted that the first particles and the second particles each contain pigment and do not move without an electric field. Moreover, the colors of the first particles and the second particles are different from each other (the colors include colorless or achroma).

[0168] In this way, an electrophoretic display is a display that utilizes a so-called dielectrophoretic effect by which a substance that has a high dielectric constant move to a high-electric field region. An electrophoretic display does not need to use a polarizer and a counter substrate, which are required in a liquid crystal display device, and both the thickness and weight of the electrophoretic display device can be a half of those of a liquid crystal display device.

[0169] A solution in which the aforementioned microcapsules are dispersed in a solvent is referred to as electronic ink. This electronic ink can be printed on a surface of glass, plastic, cloth, paper, or the like. Furthermore, by use of a color filter or particles that have a pigment, color display is possible, as well.

[0170] In addition, an active matrix type display device can be completed by providing as appropriate, a plurality of the microcapsules over an active matrix substrate so as to be interposed between two electrodes, and can perform display by application of electric field to the microcapsules. For example, the active matrix substrate obtained using the thin film transistors which can be formed together with a non-linear element by a method similar to the method for manufacturing the non-linear element described in Embodiment 2 or 3 can be used.

[0171] Note that the first particles and the second particles in the microcapsule may be formed from one of a conductive material, an insulating material, a semiconductor material, a magnetic material, a liquid crystal material, a ferroelectric material, an electroluminescent material, an electrochromic material, and a magnetophoretic material or a composite material thereof.

[0172] Through the above steps, in the connection structure between the first oxide semiconductor layer of the non-linear element and the wiring layers, the provision of the region which is bonded with the second oxide semiconductor layer, which has higher electrical conductivity than the first oxide semiconductor layer, or the provision of the region modified by a plasma treatment, allows stable operation as compared with a case of using only metal wirings. Accordingly, the function of the protective circuit is enhanced and the operation can be made stable. Further, it is possible to manufacture a highly-reliable display device having stable operation, by including a protective circuit including a non-linear element in which defects due to the peeling of the thin films are not easily caused.

[0173] In addition, if the first oxide semiconductor layer is damaged, electric characteristics of the non-linear element also becomes worse. However, because the channel formation region in the first oxide semiconductor layer of the non-linear element in Embodiment 5 is protected by the channel protective layer, there is no possibility that the first oxide semiconductor layer is damaged in the etching step of the conductive film serving as a source electrode and a drain electrode and in the etching step of the second oxide semiconductor layer. Therefore, the non-linear element of Embodiment 5, in which the channel formation region is protected by the channel protective layer, has high reliability, and a display device including a protective circuit using the non-linear element also has high reliability.

[0174] Embodiment 5 can be implemented in combination with any structure of the other embodiments as appropriate.

Embodiment 6

[0175] A thin film transistor can be manufactured together with a non-linear element according to one embodiment of the present invention, and the thin film transistor can be used for a pixel

portion and further for a driver circuit, so that a semiconductor device having a display function (also called a display device) can be manufactured. Moreover, a thin film transistor and a non-linear element according to one embodiment of the present invention can be used for part of a driver circuit or an entire driver circuit formed over one substrate together with a pixel portion, so that a system-on-panel can be formed.

[0176] The display device includes a display element. As the display element, a liquid crystal element (also referred to as a liquid crystal display element) or a light-emitting element (also referred to as a light-emitting display element) can be used. A light-emitting element includes, in its scope, an element whose luminance is controlled by current or voltage, and specifically includes an inorganic electroluminescent (EL) element, an organic EL element, and the like. Further, a display medium whose contrast is changed by an electric effect, such as electronic ink, can be used.

[0177] In addition, the display device includes a panel in which a display element is sealed, and a module in which an IC and the like including a controller are mounted on the panel. One embodiment of the present invention relates to one mode of an element substrate before the display element is completed in a process for manufacturing the display device, and the element substrate is provided with a means for supplying current to the display element in each of a plurality of pixels. Specifically, the element substrate may be in a state provided with only a pixel electrode of the display element, a state after a conductive film to be a pixel electrode is formed and before the conductive film is etched to form the pixel electrode, or any other states.

[0178] A display device in this specification refers to an image display device, a display device, or a light source (including a lighting device). Further, the display device includes any of the following modules in its category: a module including a connector such as an flexible printed circuit (FPC), a tape automated bonding (TAB) tape, or a tape carrier package (TCP); a module having a TAB tape or a TCP which is provided with a printed wiring board at the end thereof; and a module having an integrated circuit (IC) which is directly mounted on a display element by a chip-on-glass (COG) method.

[0179] The appearance and a cross section of a liquid crystal display panel, which is one mode of a display device according to one embodiment of the present invention, will be described in Embodiment 6 with reference to FIGS. 17A and 17B. FIG. 17A is a top view of a panel in which thin film transistors **4010** and **4011** with high electrical characteristics which can be manufactured together with a non-linear element by a method similar to the method for manufacturing the non-linear element, and a liquid crystal element **4013** are sealed with a sealing material **4005** between a first substrate **4001** and a second substrate **4006**. FIG. 17B corresponds to a cross section thereof along M-N of FIGS. 17A1 and 17A2.

[0180] The sealing material **4005** is provided so as to surround a pixel portion **4002** and a scan line driver circuit **4004** which are provided over the first substrate **4001**. The second substrate **4006** is provided over the pixel portion **4002** and the scan line driver circuit **4004**. Thus, the pixel portion **4002** and the scan line driver circuit **4004** as well as a liquid crystal layer **4008** are sealed with the sealing material **4005** between the first substrate **4001** and the second substrate **4006**. A signal line driver circuit **4003** that is formed using a single crystal semiconductor film or a polycrystalline semiconductor film over a substrate which is prepared separately is mounted in a region that is different from the region surrounded by the sealing material **4005** over the first substrate **4001**.

[0181] Note that there is no particular limitation on a connection method of the driver circuit which is separately formed, and a known COG method, wire bonding method, TAB method, or the like can be used. FIG. 17A1 illustrates an example in which the signal line driver circuit **4003** is mounted by a COG method and FIG. 17A2 illustrates an example in which signal line driver circuit **4003** is mounted by a TAB method.

[0182] Each of the pixel portion **4002** and the scan line driver circuit **4004** which are provided over the first substrate **4001** includes a plurality of thin film transistors. FIG. 17B illustrates the thin film transistor **4010** included in the pixel portion **4002** and the thin film transistor **4011** included in the

scan line driver circuit **4004**. Insulating layers **4020** and **4021** are provided over the thin film transistors **4010** and **4011**.

[0183] Each of the thin film transistors **4010** and **4011** has high electrical characteristics, in which an oxide semiconductor including In, Ga and Zn is used for its semiconductor layer and its source and drain regions, and can be manufactured together with a non-linear element by a method similar to the method for manufacturing the non-linear element described in Embodiment 2 or 3. In Embodiment 6, the thin film transistors **4010** and **4011** are n-channel thin film transistors.

[0184] A pixel electrode layer **4030** included in the liquid crystal element **4013** is electrically connected to the thin film transistor **4010**. A counter electrode layer **4031** of the liquid crystal element **4013** is formed on the second substrate **4006**. A portion where the pixel electrode layer **4030**, the counter electrode layer **4031**, and the liquid crystal layer **4008** overlap with each other corresponds to the liquid crystal element **4013**. Note that the pixel electrode layer **4030** and the counter electrode layer **4031** are provided with an insulating layer **4032** and an insulating layer **4033** serving as orientation films, respectively, and has the liquid crystal layer **4008** therebetween, with the insulating layers **4032** and **4033** therebetween.

[0185] Note that the first substrate **4001** and the second substrate **4006** can be formed from glass, metal (typically, stainless steel), ceramic, or plastic. As plastic, a fiberglass-reinforced plastics (FRP) plate, a polyvinyl fluoride (PVF) film, a polyester film, or an acrylic resin film can be used. In addition, a sheet with a structure in which an aluminum foil is sandwiched between PVF films or polyester films can be used.

[0186] A columnar spacer **4035**, which is formed by etching an insulating film selectively, is provided to control a distance (a cell gap) between the pixel electrode layer **4030** and the counter electrode layer **4031**. Alternatively, a spherical spacer may be used.

[0187] Alternatively, a blue phase liquid crystal without an orientation film may be used. A blue phase is a type of liquid crystal phase, which appears just before a cholesteric liquid crystal changes into an isotropic phase when the temperature of the cholesteric liquid crystal is increased. A blue phase appears only within narrow temperature range; therefore, the liquid crystal layer **4008** is formed using a liquid crystal composition in which a chiral agent of 5 wt. % or more is mixed in order to expand the temperature range. The liquid crystal composition including a blue phase liquid crystal and a chiral agent has a short response time of 10 μ s to 100 μ s, and is optically isotropic; therefore, orientation treatment is not necessary and viewing angle dependence is small. Note that Embodiment 6 describes an example of a transmissive liquid crystal display device; however, one embodiment of the present invention can be applied to a reflective liquid crystal display device or a semi-transmissive liquid crystal display device.

[0188] Although a liquid crystal display device of Embodiment 6 has a polarizer provided outer than the substrate (the viewer side) and a color layer and an electrode layer of a display element provided inner than the substrate, which are arranged in that order, the polarizer may be inner than the substrate. The stacked structure of the polarizer and the color layer is not limited to that described in Embodiment 6 and may be set as appropriate in accordance with the materials of the polarizer and the color layer and the condition of the manufacturing process. Further, a light-blocking film serving as a black matrix may be provided.

[0189] In Embodiment 6, in order to reduce the unevenness of the surface of the thin film transistors and to improve the reliability of the thin film transistors, the non-linear element described in Embodiment 2 or 3 and the thin film transistors which can be formed together with a non-linear element by a method similar to the method for manufacturing the non-linear element are covered with protective films or insulating layers (the insulating layers **4020** and **4021**) serving as planarizing insulating films. Note that the protective film is provided to prevent entry of a contaminant impurity such as an organic substance, a metal substance, or moisture existing in air, and therefore a dense film is preferable. The protective film may be formed using a single layer or a stack of layers of a silicon oxide film, a silicon nitride film, a silicon oxynitride film, a silicon

nitride oxide film, an aluminum oxide film, an aluminum nitride film, an aluminum oxynitride film, or an aluminum nitride oxide film. Although the protective film is formed by a sputtering method in Embodiment 6, the method is not limited to a particular method and may be selected from a variety of methods.

[0190] Here, the insulating layer **4020** is formed to have a stacked structure as the protective film. Here, a silicon oxide film is formed by a sputtering method as a first layer of the insulating layer **4020**. The use of a silicon oxide film for the protective film provides an advantageous effect of preventing hillock of an aluminum film used for a source electrode layer and a drain electrode layer.

[0191] Moreover, an insulating layer is formed as a second layer of the protective film. Here, a silicon nitride film is formed by a sputtering method as a second layer of the insulating layer **4020**. When a silicon nitride film is used for the protective film, it is possible to prevent movable ions such as sodium from entering a semiconductor region to vary the electrical characteristics of the TFT.

[0192] Further, after the protective film is formed, the IGZO semiconductor layer may be annealed (at 300° C. to 400° C.).

[0193] Further, the insulating layer **4021** is formed as the planarizing insulating film. The insulating layer **4021** can be formed from an organic material having heat resistance, such as polyimide, acrylic, benzocyclobutene, polyamide, or epoxy. As an alternative to such organic materials, it is possible to use a low-dielectric constant material (a low-k material), a siloxane-based resin, PSG (phosphosilicate glass), BPSG (borophosphosilicate glass), or the like. A siloxane-based resin may include as a substituent at least one of fluorine, an alkyl group, and an aryl group, as well as hydrogen. Note that the insulating layer **4021** may be formed by stacking a plurality of insulating films formed of these materials.

[0194] Note that a siloxane-based resin is a resin formed from a siloxane-based material as a starting material and having the bond of Si—O—Si. The siloxane-based resin may include as a substituent at least one of fluorine, an alkyl group, and aromatic hydrocarbon, as well as hydrogen.

[0195] The method for the formation of the insulating layer **4021** is not limited to a particular method and the following method can be used depending on the material of the insulating layer **4021**: a sputtering method, an SOG method, spin coating, dip coating, spray coating, a droplet discharge method (e.g., an inkjet method, screen printing, or offset printing), a doctor knife, a roll coater, a curtain coater, a knife coater, or the like. In the case of forming the insulating layer **4021** with use of a material liquid, annealing (300° C. to 400° C.) may be performed on the IGZO semiconductor layer at the same time as a baking step. When the baking of the insulating layer **4021** and the annealing of the IGZO semiconductor layer are performed at the same time, a semiconductor device can be manufactured efficiently.

[0196] The pixel electrode layer **4030** and the counter electrode layer **4031** can be formed from a light-transmitting conductive material such as indium oxide containing tungsten oxide, indium zinc oxide containing tungsten oxide, indium oxide containing titanium oxide, indium tin oxide containing titanium oxide, indium tin oxide (hereinafter referred to as ITO), indium zinc oxide, or indium tin oxide to which silicon oxide is added.

[0197] A conductive composition including a conductive high molecule (also referred to as a conductive polymer) can be used for the pixel electrode layer **4030** and the counter electrode layer **4031**. The pixel electrode formed of the conductive composition has preferably a sheet resistance of 10000 Ω /square or less and a transmittance of 70% or more at a wavelength of 550 nm. Further, the resistivity of the conductive high molecule included in the conductive composition is preferably 0.1 Ω .cm or less.

[0198] As the conductive high molecule, a so-called π -electron conjugated conductive polymer can be used. As examples thereof, polyaniline or a derivative thereof, polypyrrole or a derivative thereof, polythiophene or a derivative thereof, a copolymer of two or more kinds of them, and the

like can be given.

[0199] Further, a variety of signals and potentials are supplied from an FPC **4018** to the signal line driver circuit **4003** which is formed separately, the scan line driver circuit **4004**, and the pixel portion **4002**.

[0200] In Embodiment 6, a connecting terminal electrode **4015** is formed using the same conductive film as the pixel electrode layer **4030** included in the liquid crystal element **4013**. A terminal electrode **4016** is formed using the same conductive film as the source and drain electrode layers included in the thin film transistors **4010** and **4011**.

[0201] The connecting terminal electrode **4015** is electrically connected to a terminal of the FPC **4018** through an anisotropic conductive film **4019**.

[0202] Although FIGS. **17A** and **17B** illustrate an example in which the signal line driver circuit **4003** is formed separately and mounted on the first substrate **4001**, Embodiment 6 is not limited to this structure. The scan line driver circuit may be separately formed and then mounted, or only part of the signal line driver circuit or part of the scan line driver circuit may be separately formed and then mounted.

[0203] FIG. **18** illustrates an example in which a liquid crystal display module is formed as a semiconductor device using a TFT substrate **2600** manufactured according to one embodiment of the present invention.

[0204] FIG. **18** illustrates an example of a liquid crystal display module, in which the TFT substrate **2600** and a counter substrate **2601** are fixed to each other with a sealing material **2602**, and a pixel portion **2603** including a TFT and the like, a display element **2604** including a liquid crystal layer, and a color layer **2605** are provided between the substrates to form a display region. The color layer **2605** is necessary to perform color display. In the case of the RGB system, respective color layers corresponding to colors of red, green, and blue are provided for respective pixels. Polarizing plates **2606** and **2607** and a diffuser plate **2613** are provided outside the TFT substrate **2600** and the counter substrate **2601**. A light source includes a cold cathode tube **2610** and a reflective plate **2611**, and a circuit board **2612** is connected to a wiring circuit portion **2608** of the TFT substrate **2600** through a flexible wiring board **2609** and includes an external circuit such as a control circuit and a power source circuit. The polarizing plate and the liquid crystal layer may be stacked with a retardation plate therebetween.

[0205] For the liquid crystal display module, a TN (Twisted Nematic) mode, an IPS (In-Plane-Switching) mode, an FFS (Fringe Field Switching) mode, an MVA (Multi-domain Vertical Alignment) mode, a PVA (Patterned Vertical Alignment) mode, an ASM (Axially Symmetric aligned Micro-cell) mode, an OCB (Optically Compensated Birefringence) mode, an FLC (Ferroelectric Liquid Crystal) mode, an AFLC (AntiFerroelectric Liquid Crystal) mode or the like can be used.

[0206] Through the above steps, in the connection structure between the first oxide semiconductor layer of the non-linear element and the wiring layers, the provision of the region which is bonded with the second oxide semiconductor layer, which has higher electrical conductivity than the first oxide semiconductor layer, allows stable operation as compared with a case of using only metal wirings. Accordingly, the function of the protective circuit can be enhanced and the operation can be made stable. In addition, it is possible to manufacture a highly-reliable liquid crystal display panel having stable operation, by including a protective circuit including a non-linear element in which defects due to the peeling of the thin films are not easily caused.

[0207] In addition, if the first oxide semiconductor layer is damaged, electric characteristics of the non-linear element also becomes worse. However, because the channel formation region in the first oxide semiconductor layer of the non-linear element in Embodiment 6 is protected by the channel protective layer, there is no possibility that the first oxide semiconductor layer is damaged in the etching step of the conductive film serving as a source electrode and a drain electrode and in the etching step of the second oxide semiconductor layer. Therefore, the non-linear element of

Embodiment 6, in which the channel formation region is protected by the channel protective layer, has high reliability, and a liquid crystal display device including a protective circuit using the non-linear element also has high reliability.

[0208] Embodiment 6 can be implemented in combination with any structure of the other embodiments as appropriate.

Embodiment 7

[0209] A thin film transistor is formed together with a non-linear element according to one embodiment of the present invention, and a semiconductor device having a display function (also referred to as a display device) can be manufactured by using the thin film transistor in a pixel portion and a driver circuit.

[0210] Embodiment 7 describes an example of a light-emitting display device as a display device according to one embodiment of the present invention. As an example of a display element of the display device, here, a light-emitting element utilizing electroluminescence is used. Light-emitting elements utilizing electroluminescence are classified according to whether a light emitting material is an organic compound or an inorganic compound. In general, the former is referred to as an organic EL element, the latter as an inorganic EL element.

[0211] In an organic EL element, by application of voltage to a light-emitting element, electrons and holes are separately injected from a pair of electrodes into a layer containing a light-emitting organic compound, and thus current flows. Then, those carriers (i.e., electrons and holes) are recombined, and thus, the light-emitting organic compound is excited. When the light-emitting organic compound returns to a ground state from the excited state, light is emitted. Owing to such a mechanism, such a light emitting element is referred to as a current-excitation light emitting element.

[0212] The inorganic EL elements are classified, according to their element structures, into a dispersion type inorganic EL element and a thin-film type inorganic EL element. A dispersion type inorganic EL element has a light-emitting layer where particles of a light-emitting material are dispersed in a binder, and its light emission mechanism is donor-acceptor recombination type light emission that utilizes a donor level and an acceptor level. A thin-film type inorganic EL element has a structure where a light-emitting layer is sandwiched between dielectric layers, which are further sandwiched between electrodes, and its light emission mechanism is localized type light emission that utilizes inner-shell electron transition of metal ions. Note that an organic EL element is used as a light-emitting element in Embodiment 7.

[0213] FIG. 19 illustrates an example of a pixel structure to which digital time grayscale driving can be applied, as an example of a semiconductor device according to one embodiment of the present invention.

[0214] A structure and operation of a pixel to which digital time grayscale driving can be applied are described. In Embodiment 7, one pixel includes two n-channel transistors in each of which a channel formation region includes an IGZO semiconductor layer and which can be formed together with a non-linear element by a method similar to the method for manufacturing the non-linear element described in Embodiment 2.

[0215] A pixel **6400** includes a switching transistor **6401**, a driving transistor **6402**, a light-emitting element **6404**, and a capacitor **6403**. A gate of the switching transistor **6401** is connected to a scan line **6406**, a first electrode (one of a source electrode and a drain electrode) of the switching transistor **6401** is connected to a signal line **6405**, and a second electrode (the other of the source electrode and the drain electrode) of the switching transistor **6401** is connected to a gate of the driving transistor **6402**. The gate of the driving transistor **6402** is connected to a power supply line **6407** through the capacitor **6403**, a first electrode of the driving transistor **6402** is connected to the power supply line **6407**, and a second electrode of the driving transistor **6402** is connected to a first electrode (pixel electrode) of the light-emitting element **6404**. A second electrode of the light-emitting element **6404** corresponds to a common electrode **6408**.

[0216] The second electrode (common electrode **6408**) of the light-emitting element **6404** is set to a low power supply potential. The low power supply potential is a potential satisfying the low power supply potential < a high power supply potential when the high power supply potential is set to the power supply line **6407** is a reference. As the low power supply potential, GND, 0 V, or the like may be employed, for example. A potential difference between the high power supply potential and the low power supply potential is applied to the light-emitting element **6404** and current is supplied to the light-emitting element **6404**, so that the light-emitting element **6404** emits light. Here, in order to make the light-emitting element **6404** emit light, each potential is set so that the potential difference between the high power supply potential and the low power supply potential is greater than or equal to forward threshold voltage.

[0217] Gate capacitor of the driving transistor **6402** may be used as a substitute for the capacitor **6403**, so that the capacitor **6403** can be omitted. The gate capacitor of the driving transistor **6402** may be formed between the channel formation region and the gate electrode.

[0218] In the case of a voltage-input voltage driving method, a video signal is input to the gate of the driving transistor **6402** so that the driving transistor **6402** is in either of two states of being sufficiently turned on and turned off. That is, the driving transistor **6402** operates in a linear region. Since the driving transistor **6402** operates in a linear region, a voltage higher than the voltage of the power supply line **6407** is applied to the gate of the driving transistor **6402**. Note that a voltage higher than or equal to (voltage of the power supply line + V_{th} of the driving transistor **6402**) is applied to the signal line **6405**.

[0219] In a case of performing analog grayscale driving instead of digital time grayscale driving, the same pixel structure as that in FIG. **19** can be used by changing signal input.

[0220] In the case of performing analog grayscale driving, a voltage higher than or equal to (forward voltage of the light-emitting element **6404** + V_{th} of the driving transistor **6402**) is applied to the gate of the driving transistor **6402**. The forward voltage of the light-emitting element **6404** indicates a voltage at which a desired luminance is obtained, and includes at least forward threshold voltage. The video signal by which the driving transistor **6402** operates in a saturation region is input, so that current can be supplied to the light-emitting element **6404**. In order for the driving transistor **6402** to operate in a saturation region, the potential of the power supply line **6407** is set higher than the gate potential of the driving transistor **6402**. When an analog video signal is used, it is possible to feed current to the light-emitting element **6404** in accordance with the video signal and perform analog grayscale driving.

[0221] The pixel structure illustrated in FIG. **19** is not limited thereto. For example, a switch, a resistor, a capacitor, a transistor, a logic circuit, or the like may be added to the pixel illustrated in FIG. **19**.

[0222] Next, structures of a light-emitting element are described with reference to FIGS. **20A** to **20C**. A cross-sectional structure of a pixel is described here by taking an n-channel driving TFT as an example. TFTs **7001**, **7011**, and **7021** serving as driving TFTs used for a semiconductor device, which are illustrated in FIGS. **20A**, **20B**, and **20C**, can be formed together with a non-linear element by a method similar to the method for manufacturing the non-linear element described in Embodiment 2. The TFTs **7001**, **7011**, and **7021** have high electrical characteristics, in which an oxide semiconductor including In, Ga and Zn is used for a semiconductor layer and a source region and a drain region.

[0223] In addition, in order to extract light emitted from the light-emitting element, at least one of an anode and a cathode should be transparent to transmit light. A thin film transistor and a light-emitting element are formed over a substrate. A light-emitting element can have a top-emission structure in which light emission is extracted through the surface opposite to the substrate; a bottom-emission structure in which light emission is extracted through the surface on the substrate side; or a dual-emission structure in which light emission is extracted through the surface opposite to the substrate and the surface on the substrate side. The pixel structure according to one

embodiment of the present invention can be applied to a light-emitting element having any of these emission structures.

[0224] A light-emitting element with a top-emission structure is described with reference to FIG. 20A.

[0225] FIG. 20A is a cross-sectional view of a pixel in a case where the TFT 7001 serving as a driving TFT is an n-channel TFT and light generated in a light-emitting element 7002 is emitted to an anode 7005 side. In FIG. 20A, a cathode 7003 of the light-emitting element 7002 is electrically connected to the TFT 7001 serving as a driving TFT, and a light-emitting layer 7004 and the anode 7005 are stacked in this order over the cathode 7003. The cathode 7003 can be formed using any of a variety of conductive materials as long as it has a low work function and reflects light. For example, Ca, Al, CaF, MgAg, AlLi, or the like is preferably used. The light-emitting layer 7004 may be formed using a single layer or by stacking a plurality of layers. When the light-emitting layer 7004 is formed using a plurality of layers, the light-emitting layer 7004 is formed by stacking an electron-injecting layer, an electron-transporting layer, a light-emitting layer, a hole-transporting layer, and a hole-injecting layer in this order over the cathode 7003. It is not necessary to form all of these layers. The anode 7005 is formed using a light-transmitting conductive film such as a film of indium oxide including tungsten oxide, indium zinc oxide including tungsten oxide, indium oxide including titanium oxide, indium tin oxide including titanium oxide, indium tin oxide (hereinafter, referred to as ITO), indium zinc oxide, or indium tin oxide to which silicon oxide is added.

[0226] The light-emitting element 7002 corresponds to a region where the cathode 7003 and the anode 7005 sandwich the light-emitting layer 7004. In the case of the pixel illustrated in FIG. 20A, light is emitted from the light-emitting element 7002 to the anode 7005 side as indicated by the arrow of FIG. 20A.

[0227] Next, a light-emitting element having the bottom-emission structure is described with reference to FIG. 20B. FIG. 20B is a cross-sectional view of a pixel in the case where a driving TFT 7011 is n-channel, and light is emitted from a light-emitting element 7012 to the cathode 7013 side. In FIG. 20B, the cathode 7013 of the light-emitting element 7012 is formed over a light-transmitting conductive film 7017 which is electrically connected to the driving TFT 7011, and a light-emitting layer 7014 and an anode 7015 are stacked in this order over the cathode 7013. A light-blocking film 7016 for reflecting or blocking light may be formed so as to cover the anode 7015 when the anode 7015 has a light-transmitting property. For the cathode 7013, a variety of materials can be used as in the case of FIG. 20A as long as the cathode 7013 is a conductive film having a low work function. Note that the cathode 7013 is formed to have a thickness that can transmit light (preferably, approximately from 5 nm to 30 nm). For example, an aluminum film with a thickness of 20 nm can be used as the cathode 7013. The light-emitting layer 7014 may be formed of a single layer or by stacking a plurality of layers as in the case of FIG. 20A. The anode 7015 is not required to transmit light, but can be formed using a light-transmitting conductive material as in the case of FIG. 20A. For the light-blocking film 7016, metal or the like that reflects light can be used; however, it is not limited to a metal film. For example, a resin or the like to which black pigment is added can be used.

[0228] The light-emitting element 7012 corresponds to a region where the cathode 7013 and the anode 7015 sandwich the light-emitting layer 7014. In the case of the pixel illustrated in FIG. 20B, light is emitted from the light-emitting element 7012 to the cathode 7013 side as indicated by the arrow of FIG. 20B.

[0229] Next, a light-emitting element having a dual-emission structure is described with reference to FIG. 20C. In FIG. 20C, a cathode 7023 of a light-emitting element 7022 is formed over a light-transmitting conductive film 7027 which is electrically connected to the driving TFT 7021, and a light-emitting layer 7024 and an anode 7025 are stacked in this order over the cathode 7023. As in the case of FIG. 20A, the cathode 7023 can be formed of any of a variety of conductive materials

as long as it is conductive and has low work function. Note that the cathode **7023** is formed to have such a thickness that can transmit light. For example, an Al film having a thickness of 20 nm can be used as the cathode **7023**. The light-emitting layer **7024** may be formed using a single layer or by stacking a plurality of layers as in the case of FIG. **20A**. In a manner similar to FIG. **20A**, the anode **7025** can be formed using a light-transmitting conductive material.

[0230] The light-emitting element **7022** corresponds to a region where the cathode **7023**, the light-emitting layer **7024**, and the anode **7025** overlap with each other. In the pixel illustrated in FIG. **20C**, light is emitted from the light-emitting element **7022** to both the anode **7025** side and the cathode **7023** side as indicated by the arrows FIG. **20C**.

[0231] Although an organic EL element is described here as a light-emitting element, an inorganic EL element can be alternatively provided as a light-emitting element.

[0232] Note that Embodiment 7 describes the example in which a thin film transistor (driving TFT) which controls the driving of a light-emitting element is electrically connected to the light-emitting element, but a structure may be employed in which a current control TFT is connected between the driving TFT and the light-emitting element.

[0233] The semiconductor device described in Embodiment 7 is not limited to the structures illustrated in FIGS. **20A** to **20C**, and can be modified in various ways based on the spirit of techniques according to the present invention.

[0234] Next, the appearance and cross section of a light-emitting display panel (also referred to as a light-emitting panel) which corresponds to one mode of a semiconductor device according to the present invention will be described with reference to FIGS. **21A** and **21B**. FIG. **21A** is a top view of a panel in which a light-emitting element and a thin film transistor having high electrical characteristics, in which an oxide semiconductor including In, Ga and Zn is used for its semiconductor layer and its source and drain regions, by a method similar to the method for manufacturing a non-linear element according to one embodiment of the present invention are sealed between the first substrate and a second substrate with a sealing material, and FIG. **21B** is a cross-sectional view along H-I of FIG. **21A**.

[0235] A sealing material **4505** is provided so as to surround a pixel portion **4502**, signal line driver circuits **4503a** and **4503b**, and scan line driver circuits **4504a** and **4504b**, which are provided over a first substrate **4501**. In addition, a second substrate **4506** is formed over the pixel portion **4502**, the signal line driver circuits **4503a** and **4503b**, and the scan line driver circuits **4504a** and **4504b**. Accordingly, the pixel portion **4502**, the signal line driver circuits **4503a** and **4503b**, and the scan line driver circuits **4504a** and **4504b** are sealed, together with filler **4507**, with the first substrate **4501**, the sealing material **4505**, and the second substrate **4506**. In this manner, packaging (sealing) using a protective film (such as an attachment film or an ultraviolet curable resin film) or a cover material with high air-tightness and little degasification is preferably conducted so that the pixel portion **4502**, the signal line driver circuits **4503a** and **4503b**, and the scan line driver circuits **4504a** and **4504b** are not exposed to external air.

[0236] The pixel portion **4502**, the signal line driver circuits **4503a** and **4503b**, and the scan line driver circuits **4504a** and **4504b** formed over the first substrate **4501** each include a plurality of thin film transistors, and the thin film transistor **4510** included in the pixel portion **4502** and the thin film transistor **4509** included in the signal line driver circuit **4503a** are illustrated as an example in FIG. **21B**.

[0237] Each of the thin film transistors **4509** and **4510** has high electrical characteristics, in which an oxide semiconductor including In, Ga and Zn is used for its semiconductor layer and its source and drain regions, and can be manufactured together with a non-linear element in a manner similar to the method for manufacturing the non-linear element described in Embodiment 2. In Embodiment 7, the thin film transistors **4509** and **4510** are n-channel thin film transistors.

[0238] Moreover, reference numeral **4511** denotes a light-emitting element. A first electrode layer **4517** which is a pixel electrode included in the light-emitting element **4511** is electrically connected

to source and drain electrode layers of the thin film transistor **4510**. Note that although the light-emitting element **4511** has a stacked structure of the first electrode layer **4517**, an electroluminescent layer **4512**, and a second electrode layer **4513**, the structure of the light-emitting element **4511** is not limited to the structure described in Embodiment 7. The structure of the light-emitting element **4511** can be changed as appropriate depending on a direction in which light is extracted from the light-emitting element **4511**, or the like.

[0239] A partition **4520** is formed using an organic resin film, an inorganic insulating film, or organic polysiloxane. Particularly preferably, the partition **4520** is formed using a photosensitive material and an opening is formed over the first electrode layer **4517** so that a sidewall of the opening is formed as an inclined surface with continuous curvature.

[0240] The electroluminescent layer **4512** may be formed using a single layer or a plurality of layers stacked.

[0241] In order to prevent entry of oxygen, hydrogen, moisture, carbon dioxide, or the like into the light-emitting element **4511**, a protective film may be formed over the second electrode layer **4513** and the partition **4520**. As the protective film, a silicon nitride film, a silicon nitride oxide film, a DLC (diamond like carbon) film, or the like can be formed.

[0242] In addition, a variety of signals and potentials are supplied from FPCs **4518a** and **4518b** to the signal line driver circuits **4503a** and **4503b**, the scan line driver circuits **4504a** and **4504b**, or the pixel portion **4502**.

[0243] In Embodiment 7, a connecting terminal electrode **4515** is formed using the same conductive film as the first electrode layer **4517** included in the light-emitting element **4511**. A terminal electrode **4516** is formed using the same conductive film as the source and drain electrode layers included in the thin film transistors **4509** and **4510**.

[0244] The connecting terminal electrode **4515** is electrically connected to a terminal included in the FPC **4518a** through an anisotropic conductive film **4519**.

[0245] The second substrate **4506** located in the direction in which light is extracted from the light-emitting element **4511** should have a light-transmitting property. In that case, a light-transmitting material such as a glass plate, a plastic plate, a polyester film, or an acrylic film is used.

[0246] As the filler **4507**, an ultraviolet curable resin or a thermosetting resin as well as inert gas such as nitrogen or argon can be used. For example, polyvinyl chloride (PVC), acrylic, polyimide, an epoxy resin, a silicone resin, polyvinyl butyral (PVB), or ethylene vinyl acetate (EVA) can be used. In Embodiment 7, nitrogen is used for the filler **4507**.

[0247] In addition, if needed, optical films such as a polarizing plate, a circularly polarizing plate (including an elliptically polarizing plate), a retarder plate (a quarter-wave plate, a half-wave plate), and a color filter may be provided on an emission surface of the light-emitting element, as appropriate. Further, the polarizing plate or the circularly polarizing plate may be provided with an anti-reflection film. For example, anti-glare treatment can be performed by which reflected light is diffused in the depression/projection of the surface and glare can be reduced.

[0248] As the signal line driver circuits **4503a** and **4503b** and the scan line driver circuits **4504a** and **4504b**, driver circuits formed by using a single crystal semiconductor film or polycrystalline semiconductor film over a substrate separately prepared may be mounted. In addition, only the signal line driver circuit or only part thereof, or only the scan line driver circuit or only part thereof may be separately formed to be mounted. Embodiment 7 is not limited to the structure illustrated in FIGS. **21A** and **21B**.

[0249] Through the above steps, in the connection structure between the first oxide semiconductor layer of the non-linear element and the wiring layers, the provision of the region which is bonded with the second oxide semiconductor layer, which has higher electrical conductivity than the first oxide semiconductor layer, or the provision of the region modified by the plasma treatment, allows stable operation as compared with a case of using only metal wirings. Accordingly, the function of the protective circuit is enhanced and the operation can be made stable. Further, it is possible to

manufacture a highly-reliable light-emitting display device (display panel) having stable operation, by including a protective circuit including a non-linear element in which defects due to the peeling of the thin films are not easily caused.

[0250] In addition, if the first oxide semiconductor layer is damaged, electric characteristics of the non-linear element also becomes worse. However, because the channel formation region in the first oxide semiconductor layer of the non-linear element in Embodiment 7 is protected by the channel protective layer, there is no possibility that the first oxide semiconductor layer is damaged in the etching step of the conductive film serving as a source electrode and a drain electrode and in the etching step of the second oxide semiconductor layer. Therefore, the non-linear element of Embodiment 7, in which the channel formation region is protected by the channel protective layer, has high reliability, and a display device including a protective circuit using the non-linear element also has high reliability.

[0251] Embodiment 7 can be implemented in combination with any structure of the other embodiments as appropriate.

Embodiment 8

[0252] A display device according to one embodiment of the present invention can be applied as electronic paper. Electronic paper can be used for electronic devices of every field for displaying information. For example, electronic paper can be used for electronic book (e-book), posters, advertisement in vehicles such as trains, display in a variety of cards such as credit cards, and so on. Examples of such electronic devices are illustrated in FIGS. 22A and 22B and FIG. 23.

[0253] FIG. 22A illustrates a poster **2631** formed using electronic paper. If the advertizing medium is printed paper, the advertisement is replaced by manpower; however, when electronic paper according to one embodiment of the present invention is used, the advertisement display can be changed in a short time. Moreover, a stable image can be obtained without display deterioration. Further, the poster may send and receive information wirelessly.

[0254] FIG. 22B illustrates an advertisement **2632** in a vehicle such as a train. If the advertizing medium is printed paper, the advertisement is replaced by manpower; however, when electronic paper according to one embodiment of the present invention is used, the advertisement display can be changed in a short time without much manpower. Moreover, a stable image can be obtained without display deterioration. Further, the advertisement in vehicles may send and receive information wirelessly.

[0255] FIG. 23 illustrates an example of an electronic book device **2700**. For example, the electronic book device **2700** includes two housings **2701** and **2703**. The housings **2701** and **2703** are unified with each other by an axis portion **2711**, along which the electronic book device **2700** is opened and closed. With such a structure, operation like a paper book is achieved.

[0256] A display portion **2705** is incorporated in the housing **2701** and a display portion **2707** is incorporated in the housing **2703**. The display portion **2705** and the display portion **2707** may display one image, or may display different images. In the structure where the display portions display different images from each other, for example, the right display portion (the display portion **2705** in FIG. 23) can display text and the left display portion (the display portion **2707** in FIG. 23) can display images.

[0257] FIG. 23 illustrates an example in which the housing **2701** is provided with an operation portion and the like. For example, the housing **2701** is provided with a power supply **2721**, an operation key **2723**, a speaker **2725**, and the like. The page can be turned with the operation key **2723**. Note that a keyboard, a pointing device, and the like may be provided on the same plane as the display portion of the housing. Further, a rear surface or a side surface of the housing may be provided with an external connection terminal (an earphone terminal, a USB terminal, a terminal which can be connected with a variety of cables such as an AC adopter or a USB cable, and the like), a storage medium inserting portion, or the like. Moreover, the electronic book device **2700** may have a function of an electronic dictionary.

[0258] Further, the electronic book device **2700** may send and receive information wirelessly. Desired book data or the like can be purchased and downloaded from an electronic book server wirelessly.

[0259] In the connection structure between the first oxide semiconductor layer of the non-linear element and the wiring layers, the provision of the region which is bonded with the second oxide semiconductor layer, which has higher electrical conductivity than the first oxide semiconductor layer, or the provision of the region modified by the plasma treatment, allows stable operation as compared with a case of using only metal wirings. Accordingly, the function of the protective circuit is enhanced and the operation can be made stable. Further, it is possible to manufacture a highly-reliable electronic paper device having stable operation, by including a protective circuit including a non-linear element in which defects due to the peeling of the thin films are not easily caused.

[0260] In addition, if the first oxide semiconductor layer is damaged, electric characteristics of the non-linear element also becomes worse. However, because the channel formation region in the first oxide semiconductor layer of the non-linear element in Embodiment 8 is protected by the channel protective layer, there is no possibility that the first oxide semiconductor layer is damaged in the etching step of the conductive film serving as a source electrode and a drain electrode and in the etching step of the second oxide semiconductor layer. Therefore, the non-linear element of Embodiment 8, in which the channel formation region is protected by the channel protective layer, has high reliability, and electronic paper including a protective circuit using the non-linear element also has high reliability.

[0261] Embodiment 8 can be implemented in combination with any structure of the other embodiments as appropriate.

Embodiment 9

[0262] A semiconductor device according to one embodiment of the present invention can be applied to a variety of electronic devices (including game machines). As the electronic devices, for example, there are a television set (also called TV or a television receiver), a monitor for a computer or the like, a camera such as a digital camera, a digital video camera, a digital photo frame, a mobile phone (also called a mobile phone or a portable telephone device), a portable game machine, a portable information terminal, an audio playback device, and a large game machine such as a pachinko machine.

[0263] FIG. **24A** illustrates an example of a television set **9600**. A display portion **9603** is incorporated in a housing **9601** of the television set **9600**. The display portion **9603** can display images. Here, the housing **9601** is supported on a stand **9605**.

[0264] The television set **9600** can be operated by an operation switch of the housing **9601** or a separate remote controller **9610**. The channel and volume can be controlled with operation keys **9609** of the remote controller **9610** and the images displayed in the display portion **9603** can be controlled. Moreover, the remote controller **9610** may have a display portion **9607** in which the information outgoing from the remote controller **9610** is displayed.

[0265] Note that the television set **9600** is provided with a receiver, a modem, and the like. With the use of the receiver, general television broadcasting can be received. Moreover, when the display device is connected to a communication network with or without wires via the modem, one-way (from a sender to a receiver) or two-way (between a sender and a receiver or between receivers) information communication can be performed.

[0266] FIG. **24B** illustrates an example of a digital photo frame **9700**. For example, a display portion **9703** is incorporated in a housing **9701** of the digital photo frame **9700**. The display portion **9703** can display a variety of images, for example, displays image data taken with a digital camera or the like, so that the digital photo frame can function in a manner similar to a general picture frame.

[0267] Note that the digital photo frame **9700** is provided with an operation portion, an external

connection terminal (such as a USB terminal or a terminal which can be connected to a variety of cables including a USB cable), a storage medium inserting portion, and the like. These structures may be incorporated on the same plane as the display portion; however, they are preferably provided on the side surface or rear surface of the display portion because the design is improved. For example, a memory storing data of an image shot by a digital camera is inserted in the recording medium insertion portion of the digital photo frame, whereby the image data can be transferred into the digital photo frame **9700** and displayed on the display portion **9703**.

[0268] The digital photo frame **9700** may transmit and receive data wirelessly. The structure may be employed in which desired image data is transferred into the digital photo frame **9700** wirelessly to be displayed.

[0269] FIG. **25A** illustrates a portable game machine including a housing **9881** and a housing **9891** which are jointed with a connector **9893** so as to be able to open and close. A display portion **9882** and a display portion **9883** are incorporated in the housing **9881** and the housing **9891**, respectively. The portable game machine illustrated in FIG. **25A** additionally includes a speaker portion **9884**, a storage medium inserting portion **9886**, an LED lamp **9890**, an input means (operation keys **9885**, a connection terminal **9887**, a sensor **9888** (including a function of measuring force, displacement, position, speed, acceleration, angular speed, the number of rotations, distance, light, liquid, magnetism, temperature, chemical substance, sound, time, hardness, electric field, current, voltage, electric power, radiation, flow rate, humidity, tilt angle, vibration, smell, or infrared ray), a microphone **9889**, and the like). Needless to say, the structure of the portable game machine is not limited to the above, and may be any structure as long as a semiconductor device according to one embodiment of the present invention is provided. Moreover, another accessory may be provided as appropriate. The portable game machine illustrated in FIG. **25A** has a function of reading out a program or data stored in a storage medium to display it on the display portion, and a function of sharing information with another portable game machine by wireless communication. The portable game machine in FIG. **25A** can have a variety of functions other than those above.

[0270] FIG. **25B** illustrates an example of a slot machine **9900**, which is a large game machine. A display portion **9903** is incorporated in a housing **9901** of the slot machine **9900**. The slot machine **9900** additionally includes an operation means such as a start lever or a stop switch, a coin slot, a speaker, and the like. Needless to say, the structure of the slot machine **9900** is not limited to the above, and may be any structure as long as at least a semiconductor device according to one embodiment of the present invention is provided. Moreover, another accessory may be provided as appropriate.

[0271] FIG. **26** illustrates an example of a mobile phone **1000**. The mobile phone **1000** includes a housing **1001** in which a display portion **1002** is incorporated, and moreover includes an operation button **1003**, an external connection port **1004**, a speaker **1005**, a microphone **1006**, and the like.

[0272] Information can be input to the mobile phone **1000** illustrated in FIG. **26** by touching the display portion **1002** with a finger or the like. Moreover, making a call or text messaging can be performed by touching the display portion **1002** with a finger or the like.

[0273] There are mainly three screen modes of the display portion **1002**. The first mode is a display mode mainly for displaying an image. The second mode is an input mode mainly for inputting information such as text. The third mode is a display-and-input mode in which two modes of the display mode and the input mode are mixed.

[0274] For example, in the case of making a call or text messaging, the display portion **1002** is set to a text input mode where text input is mainly performed, and text input operation can be performed on a screen. In this case, it is preferable to display a keyboard or number buttons on almost the entire screen of the display portion **1002**.

[0275] When a detection device including a sensor for detecting inclination, such as a gyroscope or an acceleration sensor, is provided inside the mobile phone **1000**, display in the screen of the

display portion **1002** can be automatically switched by judging the direction of the mobile phone **1000** (whether the mobile phone **1000** is placed horizontally or vertically for a landscape mode or a portrait mode).

[0276] Further, the screen modes are switched by touching the display portion **1002** or operating the operation button **1003** of the housing **1001**. Alternatively, the screen modes can be switched depending on kinds of images displayed in the display portion **1002**. For example, when a signal for an image displayed in the display portion is data of moving images, the screen mode is switched to the display mode. When the signal is text data, the screen mode is switched to the input mode.

[0277] Moreover, in the input mode, when input by touching the display portion **1002** is not performed within a specified period while a signal detected by an optical sensor in the display portion **1002** is detected, the screen mode may be controlled so as to be switched from the input mode to the display mode.

[0278] The display portion **1002** can also function as an image sensor. For example, an image of a palm print, a fingerprint, or the like is taken by touching the display portion **1002** with the palm or the finger, whereby personal authentication can be performed. Moreover, when a backlight which emits near-infrared light or a sensing light source which emits near-infrared light is provided in the display portion, an image or data of a finger vein, a palm vein, or the like can be taken.

[0279] In the connection structure between the first oxide semiconductor layer of the non-linear element and the wiring layers, the provision of the region which is bonded with the second oxide semiconductor layer, which has higher electrical conductivity than the first oxide semiconductor layer, or the provision of the region modified by the plasma treatment, allows stable operation as compared with a case of using only metal wirings. Accordingly, the function of the protective circuit is enhanced and the operation can be made stable. Further, it is possible to manufacture a highly-reliable electronic device having stable operation, by including a protective circuit including a non-linear element in which defects due to the peeling of the thin films are not easily caused.

[0280] In addition, if the first oxide semiconductor layer is damaged, electric characteristics of the non-linear element also becomes worse. However, because the channel formation region in the first oxide semiconductor layer of the non-linear element in Embodiment 9 is protected by the channel protective layer, there is no possibility that the first oxide semiconductor layer is damaged in the etching step of the conductive film serving as a source electrode and a drain electrode and in the etching step of the second oxide semiconductor layer. Therefore, the non-linear element of Embodiment 9, in which the channel formation region is protected by the channel protective layer, has high reliability, and an electronic device including a protective circuit using the non-linear element also has high reliability.

[0281] Embodiment 9 can be implemented in combination with any structure of the other embodiments as appropriate.

[0282] This application is based on Japanese Patent Application serial no. 2008-241743 filed with Japan Patent Office on Sep. 19, 2008, the entire contents of which are hereby incorporated by reference.

Claims

1. A semiconductor device comprising: a first transistor; and a second transistor, wherein a gate electrode of the first transistor is electrically connected to one of a source electrode and a drain electrode of the first transistor and one of a source electrode and a drain electrode of the second transistor, and wherein a gate electrode of the second transistor is electrically connected to the other of the source electrode and the drain electrode of the second transistor and the other of the source electrode and the drain electrode of the first transistor, a first conductive layer configured to function as the gate electrode of the first transistor; a second conductive layer configured to

function as the gate electrode of the second transistor; a first oxide semiconductor layer over the first conductive layer; a second oxide semiconductor layer over the second conductive layer; a third conductive layer over the first oxide semiconductor layer and the second oxide semiconductor layer, the third conductive layer being configured to function as the one of the source electrode and the drain electrode of the first transistor and function as the one of the source electrode and the drain electrode of the second transistor; and a fourth conductive layer over the first oxide semiconductor layer and the second oxide semiconductor layer, the fourth conductive layer being configured to function as the other of the source electrode and drain electrode of the first transistor and function as the other of the source electrode and drain electrode of the second transistor, wherein in a plan view, the third conductive layer has a region intersecting with the first conductive layer, and wherein in a plan view, the fourth conductive layer overlaps with the first conductive layer and does not have a region intersecting with the first conductive layer.

2. A semiconductor device comprising: a first transistor; and a second transistor, wherein a gate electrode of the first transistor is electrically connected to one of a source electrode and a drain electrode of the first transistor and one of a source electrode and a drain electrode of the second transistor, and wherein a gate electrode of the second transistor is electrically connected to the other of the source electrode and the drain electrode of the second transistor and the other of the source electrode and the drain electrode of the first transistor, a first conductive layer configured to function as the gate electrode of the first transistor; a second conductive layer configured to function as the gate electrode of the second transistor; a silicon oxide film over the first conductive layer and the second conductive layer; a first oxide semiconductor layer in contact with an upper surface of the silicon oxide film, wherein the first oxide semiconductor layer overlaps with the first conductive layer with the silicon oxide film interposed therebetween; a second oxide semiconductor layer in contact with the upper surface of the silicon oxide film, wherein the second oxide semiconductor layer overlaps with the second conductive layer with the silicon oxide film interposed therebetween; a third conductive layer over the first oxide semiconductor layer and the second oxide semiconductor layer, the third conductive layer being configured to function as the one of the source electrode and the drain electrode of the first transistor and function as the one of the source electrode and the drain electrode of the second transistor; and a fourth conductive layer over the first oxide semiconductor layer and the second oxide semiconductor layer, the fourth conductive layer being configured to function as the other of the source electrode and drain electrode of the first transistor and function as the other of the source electrode and drain electrode of the second transistor, wherein in a plan view, the third conductive layer has a region intersecting with the first conductive layer, and wherein in a plan view, the fourth conductive layer overlaps with the first conductive layer and does not have a region intersecting with the first conductive layer.

3. A semiconductor device comprising: a first transistor; a second transistor; a third transistor; and a fourth transistor, wherein a gate electrode of the first transistor is electrically connected to one of a source electrode and a drain electrode of the first transistor, one of a source electrode and a drain electrode of the second transistor, a gate of the third transistor, one of a source electrode and a drain electrode of the third transistor, and one of a source electrode and a drain electrode of the second transistor, and wherein a gate electrode of the second transistor is electrically connected to the other of the source electrode and the drain electrode of the second transistor, the other of the source electrode and the drain electrode of the first transistor, the other of the source electrode and the drain electrode of the third transistor, a gate of the fourth transistor, and the other of the source electrode and the drain electrode of the fourth transistor, a first conductive layer configured to function as the gate electrode of the third transistor; a second conductive layer configured to function as a gate electrode of the second transistor; a first oxide semiconductor layer over the first conductive layer; a second oxide semiconductor layer over the second conductive layer; a third conductive layer over the first oxide semiconductor layer and the second oxide semiconductor

layer, the third conductive layer being configured to function as the one of the source electrode and the drain electrode of the first transistor and function as the one of the source electrode and the drain electrode of the second transistor; and a fourth conductive layer over the first oxide semiconductor layer and the second oxide semiconductor layer, the fourth conductive layer being configured to function as the other of the source electrode and drain electrode of the first transistor and function as the other of the source electrode and drain electrode of the second transistor, wherein in a plan view, the third conductive layer has a region intersecting with the first conductive layer, and wherein in a plan view, the fourth conductive layer overlaps with the first conductive layer and does not have a region intersecting with the first conductive layer.

4. The semiconductor device according to claim 1, wherein the first oxide semiconductor layer comprises In, Ga, and Zn, and wherein the second oxide semiconductor layer comprises In, Ga, and Zn.

5. The semiconductor device according to claim 2, wherein the first oxide semiconductor layer comprises In, Ga, and Zn, and wherein the second oxide semiconductor layer comprises In, Ga, and Zn.

6. The semiconductor device according to claim 3, wherein the first oxide semiconductor layer comprises In, Ga, and Zn, and wherein the second oxide semiconductor layer comprises In, Ga, and Zn.
