

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250267900

Kind Code

A1

Publication Date

August 21, 2025

Inventor(s)

CHANG; Heon Yong

SEMICONDUCTOR DEVICE INCLUDING A TRANSISTOR STRUCTURE AND A METHOD OF MANUFACTURING THE SAME

Abstract

A semiconductor device includes a substrate; a channel layer over the substrate; a gate stack and a gate spacer pattern over the channel layer; an interlayer insulating layer covering the gate stack and the gate spacer pattern; and a contact pattern vertically passing through the interlayer insulating layer to be connected to the substrate. the contact pattern includes a contact plug; and a contact barrier layer surrounding a side surface of the contact plug. The contact barrier layer includes a protrusion portion protruding toward the channel layer in a horizontal direction.

Inventors: CHANG; Heon Yong (Gyeonggi-do, KR)

Applicant: SK hynix Inc. (Gyeonggi-do, KR)

Family ID: 1000008097136

Appl. No.: 18/800129

Filed: August 12, 2024

Foreign Application Priority Data

KR 10-2024-0022412

Feb. 16, 2024

Publication Classification

Int. Cl.: H01L29/10 (20060101); **H01L21/768** (20060101); **H01L23/532** (20060101);
H01L29/08 (20060101); **H01L29/66** (20060101)

U.S. Cl.:

CPC H10D30/751 (20250101); **H01L21/76897** (20130101); **H01L23/53266** (20130101);
H10D62/151 (20250101); **H10D64/018** (20250101); **H10D64/021** (20250101);

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] The present application claims priority under 35 U.S.C 119(a) to Korean Patent Application No. 10-2024-0022412, filed on Feb. 16, 2024, which is incorporated herein by reference in its entirety.

BACKGROUND

1. Field

[0002] Various embodiments of the present disclosure relate generally to semiconductor technology and, more particularly, to a semiconductor device having a transistor structure and a method of manufacturing the semiconductor device.

2. Description of the Related Art

[0003] Semiconductor devices having a transistor structure are known. To increase the mobility of the carrier, the transistor structure in which a SiGe layer is used as a channel layer has been proposed.

SUMMARY

[0004] An embodiment of the present disclosure provides a semiconductor device including a transistor structure having a SiGe layer.

[0005] An embodiment of the present disclosure provides a method of manufacturing a semiconductor device including a transistor structure having a SiGe layer.

[0006] An embodiment of the present disclosure provides a semiconductor device having a contact pattern including a contact barrier layer having a protrusion portion.

[0007] An embodiment of the present disclosure provides a method of manufacturing a semiconductor device having a contact pattern including a contact barrier layer having a protrusion portion.

[0008] In accordance with an embodiment of the present disclosure, a semiconductor device includes a substrate; a channel layer over the substrate; a gate stack and a gate spacer pattern over the channel layer; an interlayer insulating layer covering the gate stack and the gate spacer pattern; and a contact pattern vertically passing through the interlayer insulating layer to be connected to the substrate. the contact pattern includes a contact plug; and a contact barrier layer surrounding a side surface of the contact plug. The contact barrier layer includes a protrusion portion protruding toward the channel layer in a horizontal direction.

[0009] In accordance with another embodiment of the present disclosure, a semiconductor device includes a first transistor structure disposed in a first region; and a second transistor structure disposed in a second region. The first transistor structure includes a channel layer over a substrate; a first gate stack over the channel layer; first gate spacer patterns over both side walls of the first gate stack; first source/drain regions in the substrate adjacent to the first gate spacer patterns, respectively; an interlayer insulating layer covering the first gate stack and the first gate spacer patterns; and first contact patterns vertically passing through the interlayer insulating layer to be connected to the first source/drain regions, respectively. The first contact patterns include first

contact plugs and first contact barrier layers surrounding side surfaces of the first contact plugs, respectively. The first contact barrier layers include protrusion portions protruding toward the channel layer in a horizontal direction.

[0010] In accordance with another embodiment of the present disclosure, a method of manufacturing a semiconductor device, the method includes forming a channel material layer over a substrate; forming a gate stack over the channel material layer; forming a gate spacer pattern over a side surface of the gate stack; patterning the channel material layer to form a channel layer; forming a source/drain region in the substrate; forming an interlayer insulating layer covering the gate stack and the gate spacer pattern; forming a contact hole vertically penetrating the interlayer insulating layer to expose the source/drain region and a side surface of the channel layer; partially removing the side surface of the channel layer exposed in the contact hole to form a recess region; conformally forming a contact barrier layer on an inner wall of the contact hole, wherein the contact barrier layer fills the recess region; and forming a contact plug over the contact barrier layer to fill the contact hole.

[0011] In accordance with another embodiment of the present disclosure, a method of manufacturing a semiconductor device, the method includes forming a channel material layer over a substrate in a first region; forming a first gate stack over the channel material layer; forming first gate spacer patterns on both opposite sidewalls of the first gate stack; forming a channel layer by removing portions of the channel material layer exposed outside of the gate spacer patterns; forming first source/drain regions in the substrate to be adjacent to the first gate spacer patterns; forming an interlayer insulating layer covering the first gate stack and the first gate spacer patterns; forming first contact holes vertically penetrating the interlayer insulating layer to expose the first source/drain regions and side end portions of the channel layer by performing a first etching process; partially removing the side ends of the channel layer exposed in the first contact hole to form recess regions by performing a second etching process; and conformally forming first contact barrier layers to include protrusion portions filling the recess regions over inner sidewalls and bottom surfaces of the first contact holes. The gate spacer patterns vertically overlap with the protrusion portion.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0012] FIG. 1A is a longitudinal cross-sectional view illustrating a semiconductor device according to an embodiment of the present disclosure.

[0013] FIG. 1B is an enlarged view of the region B of FIG. 1A.

[0014] FIGS. 2A to 2P are longitudinal cross-sectional views illustrating a method of manufacturing a semiconductor device according to an embodiment of the present disclosure.

DETAILED DESCRIPTION

[0015] Various embodiments of the present disclosure will be described below in more detail with reference to the accompanying drawings. The present disclosure may, however, be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the present disclosure to those skilled in the art. Throughout this disclosure, like reference numerals refer to like parts throughout the various figures and embodiments of the present disclosure.

[0016] Hereinafter, the diverse embodiments of the present disclosure will be described in detail with reference to the attached drawings.

[0017] The drawings are not necessarily to scale and in some instances, proportions may have been exaggerated in order to clearly illustrate features of the embodiments. When a first layer is referred

to as being “on” a second layer or “on” a substrate, it not only refers to a case where the first layer is formed directly on the second layer or the substrate but also a case where a third layer exists between the first layer and the second layer or the substrate.

[0018] FIG. 1A is a longitudinal cross-sectional view illustrating a semiconductor device according to an embodiment of the present disclosure. Referring to FIG. 1A, a semiconductor device according to an embodiment of the present disclosure may include a first transistor structure **100p** disposed in a first region **A1**. The semiconductor device may further include a second transistor structure **100n** disposed in a second region **A2**. The first region **A1** may be a PMOS transistor region, and the second region **A2** may be an NMOS transistor region.

[0019] Accordingly, the first transistor structure **100p** may be a PMOS transistor structure, and the second transistor structure **100n** may be an NMOS transistor structure.

[0020] The first transistor structure **100p** may include a channel layer **20**, a first gate stack **30p**, first gate spacer patterns **40p**, and first contact patterns **50p** disposed on the substrate **10**. The first transistor structure **100p** may further include first source/drain regions **15p** disposed in the substrate **10**. The first transistor structure **100p** may further include first interconnection patterns **60p** disposed on the first contact patterns **50p**.

[0021] The second transistor structure **100n** may include a second gate stack **30n**, second gate spacer patterns **40n**, and second contact patterns **50n** disposed on the substrate **10**. The second transistor structure **100n** may further include second source/drain regions **15n** disposed in the substrate **10**. The second transistor structure **100n** may further include a second interconnection pattern **60n** disposed on the second contact patterns **50n**. The second gate stack **30n** may be directly disposed on the substrate **10** without the channel layer **20**.

[0022] The semiconductor device may further include an interlayer insulating layer **25** covering and/or surrounding the first and second transistor structures **100p** and **100n**. The first and second interconnection patterns **60p** and **60n** may be disposed on the interlayer insulating layer **25**.

[0023] In the first region **A1**, the channel layer **20** may be directly formed on an upper surface of the substrate **10**. The channel layer **20** may include a silicon germanium (SiGe) layer.

[0024] The first gate stack **30p** and the first gate spacer patterns **40p** may be disposed on or over the channel layer **20**. As illustrated, a horizontal width of the channel layer **20** may be greater than a horizontal width of the first gate stack **30p**. The horizontal width of the channel layer **20** may be smaller than a total horizontal widths of the first gate stack **30p** and the first gate spacers **40p**.

[0025] The second gate stack **30n** and the second gate spacer patterns **40n** may be directly disposed on the upper surface of the substrate **10**.

[0026] The first gate stack **30p** may include a first gate insulating layer **31p**, a first gate barrier layer **33p**, a first lower gate electrode **35p**, a first upper gate electrode **37p**, and a first gate capping layer **39p** stacked in the recited order. The second gate stack **30n** may include a second gate insulating layer **31n**, a second gate barrier layer **33n**, a second lower gate electrode **35n**, a second upper gate electrode **37n**, and a second gate capping layer **39n**.

[0027] The first and second gate insulating layer **31p** and **31n** may include multiple insulating layers, respectively. For example, the first and second gate insulating layer **31p** and **31n** may each include an interfacial insulating layer, a high-k dielectric layer, and a dipole layer. The interfacial insulating layer may include an oxidized silicon (SiO.sub.2) layer or a silicon nitride (SiN) layer. The high-k dielectric layer may include at least one of a metal oxide layer, a metal inorganic compound layer, or a combination thereof. The metal oxide layer may include at least one of a hafnium oxide (HfO.sub.2) layer, an aluminum oxide layer (Al.sub.2O.sub.3), or a zirconium oxide layer (ZrO.sub.2). The metal inorganic compound may include at least one of a hafnium silicon oxide (HfSiO.sub.2) layer, a hafnium oxide (HfSiO) layer, a hafnium silicon oxide (HfSiO) layer, a hafnium silicon oxide (HfSiON), or an aluminum oxide (AlON) layer, or a combination thereof. The dipole layer may include a lanthanum oxide (La.sub.2O.sub.3) layer.

[0028] The first gate barrier layer **33p** and the second gate barrier layer **33n** may include at least

one of a titanium nitride (TiN) layer, a tantalum nitride (TaN) layer, a tungsten nitride (WN) layer, a molybdenum nitride (MoN) layer, or various metal silicide layers such as a titanium silicide (TiSi), a tantalum silicide (TaSi), a tungsten silicide (WSi), a nickel silicide (NiSi), a cobalt silicide (CoSi), or a combination thereof, respectively.

[0029] Each of the first lower gate electrode **35p** and the second lower gate electrode **35n** may include a silicon layer. For example, each of the first lower gate electrode **35p** and the second lower gate electrode **35n** may include an N-doped polysilicon layer doped with N-type ions such as phosphorous (P), arsenic (As), or antimony (Sb).

[0030] Each of the first upper gate electrode **37p** and the second upper gate electrode **37n** may include a metal such as, for example, tungsten (W), copper (Cu), or molybdenum (Mo).

[0031] In an embodiment, a diffusion barrier layer or a metal silicide layer may be further disposed between the first lower gate electrode **35p** and the first upper gate electrode **37p**, and also between the second lower gate electrode **35n** and the second upper gate electrode **37n**, respectively. The diffusion barrier layer may include at least one of a titanium nitride (TiN) layer, a tantalum nitride (TaN) layer, a molybdenum nitride (MoN) layer, and a tungsten nitride (WN) layer. The metal silicide layer may include at least one of a tungsten silicide (WSi) layer, a titanium silicide (TiSi) layer, a tantalum silicide (TaSi) layer, a nickel silicide (NiSi) layer, a cobalt silicide (CoSi) layer, or a molybdenum silicide (MoSi) layer.

[0032] Each of the first and second gate capping layers **39p** and **39n** may include a hard mask such as, for example, silicon nitride (SiN) or silicon oxynitride (SiON). For example, each of the first and second gate capping layers **39p** and **39n** may include an insulating layer.

[0033] In an embodiment, the first gate stack **30p** may not include at least one of the first gate insulating layer **31p**, the first gate barrier layer **33p**, the first lower gate electrode **35p**, the first upper gate electrode **37p**, and the first gate capping layer **39p**. In an embodiment, the second gate stack **30n** may not include at least one of the second gate insulating layer **31n**, the second gate barrier layer **33n**, the second lower gate electrode **35n**, the second upper gate electrode **37n**, and the second gate capping layer **39n**.

[0034] Sidewalls of the first gate insulating layer **31p**, the first gate barrier layer **33p**, the first lower and upper gate electrodes **35p** and **37p**, and the first gate capping layer **39p** may be vertically aligned with one another to be vertically coplanar. Sidewalls of the second gate insulating layer **31n**, the second gate barrier layer **33n**, the second lower and upper gate electrodes **35n** and **37n**, and the second gate capping layer **39n** may be vertically aligned with one another to be vertically coplanar.

[0035] The first gate spacer patterns **40p** may include first inner gate spacers **41p**, first intermediate gate spacers **43p**, and first outer gate spacers **45p**. The second gate spacer patterns **40n** may include second inner gate spacers **41n**, second intermediate gate spacers **43n**, and second outer gate spacers **45n**.

[0036] The first and second inner gate spacers **41p** and **41n** may have an L-shaped cross section, respectively. For example, each of the first inner gate spacers **41p** may be disposed on opposite sidewalls of the first gate stack **30p** and portions of the upper surface of the channel layer **20**. Likewise, the second inner gate spacers **41n** may be disposed on both opposite sidewalls of the second gate stack **30n** and portions of the upper surface of the substrate **10**. Each of the first inner gate spacers **41p** and the second inner gate spacers **41n** may include silicon nitride (SiN), respectively.

[0037] One side surface and a lower surface of each of the first intermediate gate spacers **43p** and the second intermediate gate spacers **43n** may be in contact with the first inner gate spacers **41p** and the second inner gate spacers **41n**, respectively. The first intermediate gate spacers **43p** and the second intermediate gate spacers **43n** may include silicon oxide (SiO₂), respectively.

[0038] The first outer gate spacers **45p** and the second outer gate spacers **45n** may have a curved shape conformally disposed on the outer surfaces of the first intermediate gate spacers **43p** and the

second intermediate gate spacers **43n**, respectively. The first and second outer gate spacers **45p** and **45n** may include silicon nitride (SiN), respectively. The first outer gate spacers **45p** and the second outer gate spacers **45n** may be in contact with the first inner gate spacers **41p** and the second inner gate spacers **41n**, respectively, at uppermost ends and lowermost ends.

[0039] The first contact patterns **50p** may vertically pass through the interlayer insulating layer **25** to connect the first source/drain regions **15p** to the first interconnection patterns **60p**. The second contact patterns **50n** may vertically pass through the interlayer insulating layer **25** to connect the second source/drain regions **15n** to the second interconnection patterns **60n**.

[0040] The first contact patterns **50p** may include first contact barrier layers **51p** and first contact plugs **53p**, respectively. The second contact patterns **50n** may include second contact barrier layers **51n** and second contact plugs **53n**, respectively. The first contact barrier layers **51p** may conformally surround side surfaces and bottom surfaces of the first contact plugs **53p**. The second contact barrier layers **51n** may conformally surround side surfaces and bottom surfaces of the second contact plugs **53n**. For example, each of the first contact barrier layers **51p** and the second contact barrier layers **51n** may have a tube shape or a cylinder shape. Each of the first contact barrier layers **51p** and the second contact barrier layers **51n** may include one of a titanium nitride (TiN) layer, a tantalum nitride (TaN) layer, a tungsten nitride (WN) layer, and other metal nitride layers. Each of the first contact plugs **53p** and the second contact plugs **53n** may have a pillar shape filling the space within the tube or cylinder shape formed by the respective first and second contact barrier layers **51p** and **51n**. Each of the first contact plugs **53p** and the second contact plugs **53n** may include a metal such as, for example, tungsten (W).

[0041] The first interconnection patterns **60p** may include first interconnection barrier layers **61p** disposed on the first contact patterns **50p** and first interconnection lines **63p** disposed on the first interconnection barrier layers **61p**. The second interconnection patterns **60n** may include second interconnection barrier layers **61n** disposed on the second contact patterns **50n** and second interconnection lines **63n** disposed on the second interconnection barrier layers **61n**. The first interconnection barrier layers **61p** and the second interconnection barrier layers **61n** may include a titanium nitride (TiN) layer. In an embodiment, the first interconnection barrier layers **61p** and the second interconnection barrier layers **61n** may include a tantalum nitride (TaN) layer or a tungsten nitride (WN) layer. The first interconnection lines **63p** and the second interconnection lines **63n** may include a metal such as, for example, tungsten (W). In an embodiment, the first interconnection barrier layers **61p** and the second interconnection barrier layers **61n** may further include metal silicide layers disposed on the first contact patterns **50p** and the second contact patterns **50n**, respectively. The metal silicide layers may include one of cobalt silicide (CoSi), titanium silicide (TiSi), tungsten silicide (WSi), tantalum silicide (TaSi), nickel silicide (NiSi), or other metal silicides.

[0042] FIG. 1B is an enlarged view of the region B of FIG. 1A. Referring to FIG. 1B, the channel layer **20** may be recessed in a horizontal direction between the first gate spacer pattern **40p** and the substrate **10**, or, in particular, between the first gate spacer pattern **40p** and the first source/drain regions **15p**.

[0043] The first contact barrier layer **51p** of the first contact pattern **50p** may protrude toward the channel layer **20**. That is, the first contact barrier layer **51p** may have a protrusion portion P protruding to the channel layer **20**. The protrusion portion P may also be referred to as a horizontal extension of the first contact barrier layer **51p**.

[0044] In the horizontal direction, a side end portion of the channel layer **20** may be located in a middle of the first gate spacer pattern **40p**. Accordingly, a recessed horizontal depth DP of the channel layer **20** or a horizontal length DP of the protrusion portion P may be smaller than a horizontal width WS of the first gate spacer pattern **40p**. The first source/drain regions **15p** may extend and expand to a lower portion of the recessed side end portion of the channel layer **20**. The first source/drain regions **15p** may be in contact with the lower surface of the protrusion P.

[0045] The protrusion portion P and the channel layer **20** may be located at the same horizontal level. More specifically, an upper surface (a top surface) of the channel layer **20** and an upper surface of the protrusion portion P may be coplanar, and a lower surface (a bottom surface) of the channel layer **20** and a lower surface of the protrusion portion P may be coplanar. The protrusion portion P may be directly in contact with a side end of the channel layer **20**. The first gate spacer pattern **40p** may vertically overlap the protrusion portion P.

[0046] The protrusion portion P of the first contact barrier layer **51p** of the first contact pattern **50p** is advantageous because it may prevent metal atoms (e.g., tungsten (W) atoms) diffusing or penetrating from the first contact plug **53p** into the channel layer **20**.

[0047] FIGS. 2A to 2P are longitudinal cross-sectional views illustrating a method of manufacturing a semiconductor device according to an embodiment of the present disclosure. Referring now to FIG. 2A, a method of manufacturing a semiconductor device, according to an embodiment of the present disclosure, may include forming a buffer oxide layer **15** in common over a first region A1 and a second region A2 of a substrate **10**. The first region A1 may include a PMOS transistor region. The second region A2 may include an NMOS transistor region.

[0048] The substrate **10** may include a semiconductor material layer. Any suitable semiconductor material may be used. For example, the substrate **10** may include one of a silicon wafer, an epitaxial growth layer such as silicon germanium (SiGe) or silicon carbide (SiC), or a silicon layer including at least one of aluminum (Al), gallium (Ga), arsenic (As), phosphorus (P), boron (B), antimony (Sb), or other impurities.

[0049] The buffer oxide layer **15** may be commonly formed in the first region A1 and the second region A2. Forming the buffer oxide layer **15** may include performing an oxidation process to oxidize a surface of the substrate **10** to form an oxidized silicon layer. In an embodiment, forming the buffer oxide layer **15** may include forming a silicon oxide layer over the surface of the substrate **10** by performing a deposition process such as chemical vapor deposition (CVD).

[0050] Referring to FIG. 2B, the method may further include removing the buffer oxide layer **15** in the first region A1. For example, the method may include forming a first mask pattern M1 that exposes the first region A1 and covers the second region A2. Then the process may include removing the oxide layer **15** over the substrate **10** in the first region A1 via, for example, by an etching process or another suitable removing process using the first mask pattern M1 as an etching mask to protect the oxide over the second region A2. Thus, the surface of the substrate **10** may be exposed in the first region A1.

[0051] The first mask pattern M1 may include any suitable photoresist. Thereafter, the method may further include removing the first mask pattern M1.

[0052] Referring to FIG. 2C, the method may further include forming a channel material layer **20a** over the exposed substrate **10** in the first region A1. Forming the channel material layer **20a** may include forming a silicon germanium (SiGe) layer over the substrate **10** by performing an epitaxial growth process.

[0053] Referring to FIG. 2D, the method may further include removing the buffer oxide layer **15** in the second region A2. For example, the method may further include forming a second mask pattern M2 that covers the first region A1 and exposes the second region A2, and performing an etching process or a removal process using the second mask pattern M2 as an etching mask to remove the buffer oxide layer **15** only over the substrate **10** in the second region A2. The surface of the substrate **10** may be exposed in the second area A2.

[0054] The second mask pattern M2 may include any suitable photoresist. Thereafter, the method may further include removing the second mask pattern M2.

[0055] Referring to FIG. 2E, the method may further include forming first and second gate stacks **30p** and **30n** over the first and second regions A1 and A2, respectively. The first gate stack **30p** may be formed over the channel material layer **20a** in the first region A1 and the second gate stack **30n** may be formed over the substrate **10** in the second region A2. For example, the first gate stack **30p**

may include a PMOS gate stack, and the second gate stack **30n** may include an NMOS gate stack. [0056] The first gate stack **30p** may include a first gate insulating layer **31p**, a first gate barrier layer **33p**, a first lower gate electrode **35p**, a first upper gate electrode **37p**, and a first gate capping layer **39p**. The second gate stack **30n** may include a second gate insulating layer **31n**, a second gate barrier layer **33n**, a second lower gate electrode **35n**, a second upper gate electrode **37n**, and a second gate capping layer **39n**.

[0057] Forming the gate stacks **30p** and **30n** may include forming a gate insulating material layer, a gate barrier material layer, a lower gate electrode material layer, an upper gate electrode material layer, and a gate capping material layer, and performing a photolithography process and a patterning process (i.e., an etching process).

[0058] Forming the gate insulating material layer may include forming multiple insulating layers. For example, the gate insulating material layer may include an interfacial insulating material layer, a high-k dielectric material layer, and a dipole material layer. The interfacial insulating material layer may include a channel material layer **20a** or an oxidized silicon (SiO₂) layer obtained by oxidizing a surface of the substrate **10**. In an embodiment, the interfacial insulating material layer may include a deposited silicon oxide (SiO₂) layer. The high-k dielectric material layer may include a metal such as hafnium. For example, the high-k dielectric layer may include a hafnium oxide (HfO₂) layer or a hafnium silicon oxide (HfSiO₂) layer. The dipole material layer may include lanthanum (La). For example, the dipole material layer may include a lanthanum oxide (La₂O₃) layer. Accordingly, the first gate insulating layer **31p** and the second gate insulating layer **31n** may have a stacked structure of an interfacial insulating layer, a high-k dielectric layer, and a dipole layer.

[0059] Forming the gate barrier material layer may include forming a titanium nitride (TiN) layer, a tantalum nitride (TaN) layer, or a tungsten nitride (WN) layer. Accordingly, the first gate barrier layer **33p** and the second gate barrier layer **33n** may include at least one of a titanium nitride (TiN) layer, a tantalum nitride (TaN) layer, and a tungsten nitride (WN) layer.

[0060] Forming the lower gate electrode material layer may include forming a doped polysilicon layer. Accordingly, the first lower gate electrode **35p** and the second lower gate electrode **35n** may include an N-doped polysilicon layer doped with N-type ions.

[0061] Forming the upper gate electrode material layer may include forming a metal layer such as, for example, tungsten (W). Accordingly, each of the first upper gate electrode **37p** and the second upper gate electrode **37n** may include a metal such as, for example, tungsten (W).

[0062] In an embodiment, a diffusion barrier material layer or a metal silicide layer (not shown) may be further formed between the lower gate electrode material layer and the upper gate electrode material layer. The diffusion barrier layer may include at least one of a titanium nitride (TiN) layer, a tantalum nitride (TaN) layer, and a tungsten nitride (WN) layer. The metal silicide layer may include at least one of a tungsten silicide (WSi) layer, a titanium silicide (TiSi) layer, a tantalum silicide (TaSi) layer, a nickel silicide (NiSi) layer, or a cobalt silicide (CoSi) layer.

[0063] Forming the gate capping material layer may include forming a hard mask such as, for example, silicon nitride (SiN) or silicon oxynitride (SiON) over the upper gate electrode material layer. Accordingly, each of the first and second gate capping layers **39p** and **39n** may include a hard mask such as, for example, silicon nitride (SiN) or silicon oxynitride (SiON). For example, the first and second gate capping layers **39p** and **39n** may each include an insulating layer. In the first area **A1**, a surface of the channel material layer **20a** may be exposed, while in the second area **A2**, the surface of the substrate **10** may be exposed.

[0064] Referring to FIG. 2F, the method may further include forming first and second inner gate spacer material layers **41pa** and **41na** and first and second intermediate gate spacer material layers **43pa** and **43na**. Forming the first and second inner gate spacer material layers **41pa** and **41na** and forming the first and second intermediate gate spacer material layers **43pa** and **43na** may include performing a deposition process such as CVD, respectively. The first inner gate spacer material

layers **41pa** may be conformally formed on both opposite sidewalls and an upper surface of the first gate stack **30p**, and the exposed surface of the channel material layer **20a**. The second inner gate spacer material layers **41na** may be conformally formed on both opposite sidewalls and an upper surface of the second gate stack **30n**, and the exposed surface of the substrate **10**.

[0065] The first and second intermediate gate spacer material layers **43pa** and **43na** may be conformally formed on the first and second inner gate spacer material layers **41pa** and **41na**, respectively. The first and second inner gate spacer material layers **41pa** and **41na** may include a silicon nitride (SiN) layer. The first and second intermediate gate spacer material layers **43pa** and **43na** may include a silicon oxide (SiO₂) layer.

[0066] Referring to FIG. 2G, the method may further include forming first and second inner gate spacers **41p** and **41n** and first and second intermediate gate spacers **43p** and **43n** on both opposite sidewalls of the first and second gate stacks **30p** and **30n** by performing a first etch-back process. Upper surfaces of the first and second gate capping layers **39p** and **39n** may be exposed. The upper surface of the channel material layer **20a** may be exposed in the first area **A1**. The upper surface of the substrate **10** may be exposed in the second area **A2**. The first inner gate spacers **41p** may be conformally formed in an L-shape on both opposite side surfaces of the first gate stack **30p** and the exposed upper surface of the channel material layer **20a**. The second inner gate spacers **41n** may be conformally formed in an L-shape on both opposite side surfaces of the second gate stack **30n** and the exposed upper surface of the substrate **10**. That is, in the first region **A1**, the first inner gate spacers **41p** may be formed over a portion of the surface of the channel material layer **20a** adjacent to the first gate stack **30p**. In the second region **A2**, the second inner gate spacers **41n** may be formed on a portion of the surface of the substrate **10** adjacent to the second gate stack **30n**. The first and second intermediate gate spacers **43p** and **43n** may be formed on outer surfaces and upper surfaces of the first and second inner gate spacers **41p** and **41n**, respectively. In the first region **A1**, the first intermediate gate spacers **43p** may be formed on the first inner gate spacers **41p** formed on a portion of the channel material layer **20a**. In the second region **A2**, the second intermediate gate spacers **43n** may be formed on the second inner gate spacers **41n** formed on a portion of the substrate **10**.

[0067] Referring to FIG. 2H, the method may further include forming first and second outer gate spacer material layers **45pa** and **45na**, for example, via a deposition process such as a CVD. The first and second outer gate spacer material layers **45pa** and **45na** may be conformally formed on the upper surfaces of exposed first and second gate capping layers **39p** and **39n** of the first and second gate stacks **30p** and **30n**, surfaces of the first and second intermediate gate spacers **43pa** and **43na**, the upper surface of the channel material layer **20a** exposed in the first region **A1**, and the upper surface of the substrate **10** exposed in the second region **A2**, respectively. The first and second outer gate spacer material layers **45pa** and **45na** may include a silicon nitride (SiN) layer.

[0068] Referring to FIG. 2I, the method may further include performing a second etch-back process to form first and second external gate spacers **45p** and **45n**. The first and second outer gate spacers **45p** and **45n** may be formed over the first and second intermediate gate spacers **43p** and **43n**, respectively. First gate spacer patterns **40p** including first inner gate spacers **41p**, first intermediate gate spacers **43p**, and first outer gate spacers **45p** may be formed. Second gate spacer patterns **40n** including second inner gate spacers **41n**, second intermediate gate spacers **43n**, and second outer gate spacers **45n** may be formed.

[0069] In the first area **A1**, portions of the channel material layer **20a** exposed outside of the gate spacer pattern **40n** may be removed so that the surface of the substrate **10** may be exposed. The channel material layer **20a** may remain under the first gate stack **30p** and the first and second spacer patterns **40p** and **40n** to be formed as a preliminary channel layer **20p**. In the first region **A1**, first gate spacer patterns **40p** including first inner gate spacers **41p**, first intermediate gate spacers **43p**, and first outer gate spacers **45p** may be formed. In the second region **A2**, second gate spacer patterns **40n** may be formed to include second inner gate spacers **41n**, second intermediate gate

spacers **43n**, and second outer gate spacers **45n**. In the first region **A1**, outer surfaces of the first outer gate spacers **45p** and both side cross-sections of the preliminary channel layer **20p** may be vertically aligned.

[0070] Referring to FIG. 2J, the method may further include forming first source/drain regions **15p** and second source/drain regions **15n** by performing an ion implantation process. The first source/drain regions **15p** may be formed in the substrate **10** in regions which are adjacent to side surfaces of the first gate spacer patterns **40p** and both side ends of the preliminary channel layer **20p** in the first region **A1**. The second source/drain regions **15n** may be formed in the substrate **10** adjacent to side surfaces of the second gate spacer patterns **40n** in the second region **A2**. The first source/drain regions **15p** may include boron (B). The second source/drain regions **15n** may include arsenic (As) and/or phosphorus (P). The first and second outer gate spacer material layers **45pa** and **45na** may be thinned to be formed as first and second outer gate spacer layers **45p** and **45n**.

[0071] The first source/drain regions **15p** may be formed by performing a first ion doping process after forming a first mask pattern (for example, refer to the first mask pattern **M1** of FIG. 2B) that exposes the first region **A1** and covers the second region **A2**. The second source/drain regions **15n** may be formed by performing a second ion doping process after forming a mask pattern (for example, refer to the second mask pattern **M2** of FIG. 2D) covering the first region **A1** and exposing the second region **A2**. The first source/drain regions **15p** may horizontally extend and expand to lower portions of the first gate spacer patterns **40p** and lower portions of the preliminary channel layer **20p**. The second source/drain regions **15n** may horizontally extend and expand to lower portions of the second gate spacer patterns **40n**.

[0072] Referring to FIG. 2K, the method may further include forming an interlayer insulating layer **25** as a whole in the first region **A1** and the second region **A2**. The interlayer insulating layer **25** may include a silicon oxide (SiO_2) layer. The method may further include planarizing an upper surface of the interlayer insulating layer **25** by performing a planarization process such as CMP.

[0073] Referring to FIG. 2L, the method may further include forming the first and second contact holes **Hp** and **Hn** by performing a first etching process. The first and second contact holes **Hp** and **Hn** may vertically penetrate the interlayer insulating layer **25** to expose the first source/drain regions **15p** and the second source/drain regions **15n**, respectively. The lowermost surfaces of the first and second contact holes **Hp** and **Hn** may be positioned lower than the top surface of the substrate **10**. For example, surfaces of the first source/drain regions **15p** and the second source/drain regions **15n** exposed in the first and second contact holes **Hp** and **Hn** may be recessed.

[0074] Referring to FIG. 2M, the method may further include performing a second etching process to form recess regions **R** in the first contact holes **Hp** in the first region **A1**. The recess regions **R** may be formed by partially removing both ends of the preliminary channel layer **20p**. The second etching process may include selectively removing the preliminary channel layer **20p**, for example, silicon germanium (SiGe). Both side ends of the preliminary channel layer **20p** may be partially removed to be formed into the channel layer **20**.

[0075] FIG. 2N is an enlarged view of the 'C' area of FIG. 2M. Referring to FIG. 2N, the recess region **R** may be formed under a portion of the first gate space pattern **40p**. A horizontal width **WS** of the first gate spacer pattern **40p** may be greater than a horizontal depth **DR** of the recess region **R**. The side end portion of the channel layer **20** may be horizontally located in a middle of the first gate spacer pattern **40p**. Side end portions of the first source/drain regions **15p** may be located under the channel layer **20**.

[0076] Referring to FIG. 2O, the method may further include conformally forming first and second contact barrier material layers **51pa** and **51na** on inner walls and bottom surfaces of the first and second contact holes **Hp** and **Hn**. In the first region **A1**, the first contact barrier material layer **51pa** may fill the recess region **R**. That is, the first contact barrier material layer **51pa** may form a protrusion portion **P**. Forming the first and second contact barrier material layers **51pa** and **51na** may include performing a deposition process such as CVD. The first and second contact barrier

material layers **51pa** and **51na** may include, for example, a titanium nitride (TiN) layer. In an embodiment, the first and second contact barrier material layers **51pa** and **51na** may include a tantalum nitride (TaN) layer or a tungsten nitride (WN) layer. Referring to FIG. 2P, the method may further include forming first and second contact plugs **53p** and **53n** filling the first and second contact holes Hp and Hn to form first and second contact patterns **50p** and **50n**. The method may further include performing a planarization process such as a CMP to coplanarize upper surfaces of the first and second contact patterns **50p** and **50n** and an upper surface of the interlayer insulating layer **25**.

[0077] Thereafter, referring to FIG. 1A, the method may further include forming the first and second interconnection patterns **60p** and **60n**. Forming the first and second interconnection patterns **60p** and **60n** may include performing a deposition process, a photolithography process, and a patterning process to form first and second interconnection barrier layers **61p** and **61n** and first and second interconnection lines **63** on upper surfaces of the interlayer insulating layer **25**. Forming the first and second interconnection barrier layers **61p** and **61n** may include forming a titanium nitride (TiN) layer by performing a deposition process. In an embodiment, forming the first and second interconnection barrier layers **61p** and **61n** may include forming a tantalum nitride (TaN) layer or a tungsten nitride (WN) layer by performing a deposition process. Forming the first and second interconnection lines **63p** and **63n** may include forming a metal layer such as a tungsten (W) layer by performing a deposition process. In an embodiment, forming the first and second interconnection barrier layers **61p** and **61n** may further include forming metal silicide layers on the interlayer insulating layer **25** by performing a deposition process. The metal silicide layers may include at least one of cobalt silicide (CoSi), titanium silicide (TiSi), tungsten silicide (WSi), tantalum silicide (TaSi), nickel silicide (NiSi), or other metal silicides.

[0078] According to embodiments of the present disclosure, a gap between the SiGe channel layer and the metal contact plug can be sufficiently provided, so that leakage current can be reduced.

[0079] While the present disclosure has been described with respect to the specific embodiments, it will be apparent to those skilled in the art that various changes and modifications may be made without departing from the spirit and scope of the disclosure as defined in the following claims. Furthermore, the embodiments may be combined to form additional embodiments.

Claims

1. A semiconductor device comprising: a channel layer disposed over a substrate; a gate stack and a gate spacer pattern disposed over the channel layer; an interlayer insulating layer covering the gate stack and the gate spacer pattern; and a contact pattern vertically passing through the interlayer insulating layer to be connected to the substrate, wherein the contact pattern includes: a contact plug; and a contact barrier layer surrounding a side surface of the contact plug, wherein the contact barrier layer includes a protrusion portion extending in a horizontal direction toward the channel layer.
2. The semiconductor device of claim 1, wherein a side end portion of the channel layer is recessed from an outer surface of the gate spacer pattern in the horizontal direction.
3. The semiconductor device of claim 1, wherein a side end portion of the channel layer is in contact with the protrusion portion of the contact barrier layer.
4. The semiconductor device of claim 1, wherein a gate spacer pattern vertically overlaps with the protrusion portion.
5. The semiconductor device of claim 1, wherein a horizontal width of the channel layer is greater than a horizontal width of the gate stack.
6. The semiconductor device of claim 1, wherein the gate stack includes: a gate insulating layer; a gate barrier layer; a gate electrode layer; and a gate capping layer, wherein sidewalls of the gate insulating layer, the gate barrier layer, the gate electrode layer, and the gate capping layer are

vertically coplanar.

7. The semiconductor device of claim 6, wherein the gate insulating layer includes an interfacial insulating layer, a high-k dielectric layer, and a dipole layer vertically stacked.

8. The semiconductor device of claim 1, wherein the gate spacer pattern includes: an inner gate spacer including silicon nitride; an intermediate gate spacer including silicon oxide; and an outer gate spacer layer including silicon nitride, wherein the internal gate spacer is conformally disposed on a sidewall of the gate stack and a portion of an upper surface of the channel layer to have an L-shape, wherein the intermediate gate spacer is disposed over the inner gate spacer, and wherein the outer gate spacer is conformally disposed over an outer surface of the intermediate gate spacer.

9. The semiconductor device of claim 1, wherein the channel layer includes a silicon germanium layer disposed over the substrate.

10. The semiconductor device of claim 1, wherein the contact barrier layer includes a metal nitride layer, and wherein the contact plug includes a metal.

11. A semiconductor device comprising: a first transistor structure disposed in a first region; and a second transistor structure disposed in a second region, wherein the first transistor structure includes: a channel layer over a substrate; a first gate stack over the channel layer; first gate spacer patterns over both side walls of the first gate stack; first source/drain regions in the substrate to be adjacent to the first gate spacer patterns, respectively; an interlayer insulating layer covering the first gate stack and the first gate spacer patterns; and first contact patterns vertically passing through the interlayer insulating layer to be connected to the first source/drain regions, respectively, wherein the first contact patterns include first contact plugs and first contact barrier layers surrounding side surfaces of the first contact plugs, respectively, wherein the first contact barrier layers include protrusion portions protruding toward the channel layer in a horizontal direction.

12. The semiconductor device of claim 11, wherein a horizontal width of the channel layer is greater than a horizontal width of the first gate stack.

13. The semiconductor device of claim 11, wherein a horizontal width of the channel layer is less than a sum of a horizontal width of the first gate stack and horizontal widths of the first gate spacer patterns.

14. The semiconductor device of claim 11, wherein the protrusion portions vertically overlap with the first gate spacer patterns, respectively.

15. The semiconductor device of claim 11, wherein the channel layer and the protrusion portions of the first contact barrier layers are in direct contact with each other.

16. The semiconductor device of claim 11, wherein the second transistor structure includes: a second gate stack directly disposed over the substrate; second gate spacer patterns disposed on both opposite sidewalls of the second gate stack; second source/drain regions in the substrate to be adjacent to the second gate spacer patterns, respectively; and second contact patterns vertically passing through the interlayer insulating layer and connected to the second source/drain regions, respectively, wherein the second contact patterns include second contact plugs and second contact barrier layers surrounding side surfaces of the second contact plugs, respectively.
