



US012392016B2

(12) **United States Patent**
Flores Renteria

(10) **Patent No.: US 12,392,016 B2**
(45) **Date of Patent: Aug. 19, 2025**

(54) **ALLOY, POWDER, DUCTILE GAMMA'
ADHESION PROMOTER LAYER AND
COMPONENT**

(71) Applicant: **Siemens Energy Global GmbH & Co.
KG**, Munich (DE)

(72) Inventor: **Arturo Flores Renteria**, Berlin (DE)

(73) Assignee: **Siemens Energy Global GmbH & Co.
KG**, Munich (DE)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **18/750,692**

(22) Filed: **Jun. 21, 2024**

(65) **Prior Publication Data**

US 2024/0344182 A1 Oct. 17, 2024

Related U.S. Application Data

(62) Division of application No. 18/251,916, filed as
application No. PCT/EP2021/077444 on Oct. 5,
2021.

(30) **Foreign Application Priority Data**

Nov. 5, 2020 (DE) 10 2020 213 918.0

(51) **Int. Cl.**

C22C 19/05 (2006.01)

B22F 1/10 (2022.01)

C23C 4/073 (2016.01)

C23C 28/00 (2006.01)

(52) **U.S. Cl.**

CPC **C22C 19/058** (2013.01); **B22F 1/10**
(2022.01); **C23C 4/073** (2016.01); **C23C**
28/3215 (2013.01); **C23C 28/3455** (2013.01);
B22F 2301/15 (2013.01); **B22F 2999/00**
(2013.01)

(58) **Field of Classification Search**

CPC ... C22C 19/056; C22C 19/058; C22C 19/055;
C22F 1/10; C23C 4/073; C23C 28/3215;
B22F 1/10

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,885,216 A 12/1989 Naik C30B 29/52
148/404

4,909,984 A 3/1990 Singheiser et al.

6,060,174 A 5/2000 Sabol et al.

6,482,537 B1 11/2002 Strangman et al.

7,422,769 B2 9/2008 Kassner et al.

2003/0211356 A1 11/2003 Beers C23C 4/073
420/443

2012/0048912 A1 3/2012 Hu et al.

2014/0220384 A1 8/2014 Stamm

2014/0234652 A1 8/2014 Li

FOREIGN PATENT DOCUMENTS

CN 103797141 A 5/2014

CN 108950415 A 12/2018

DE 3612588 A1 10/1987

DE 3842300 A1 * 6/1990 C23C 30/00

DE 8842301 A1 6/1990

DE 60010271 T2 5/2005

DE 60103526 T2 6/2005

DE 102004034410 A1 2/2008

EP 0241807 A2 10/1987

OTHER PUBLICATIONS

Akatsu, T. A. K. A. S. H. I., et al. "Thermal barrier coating made of
porous zirconium oxide on a nickel-based single crystal superalloy
formed by plasma electrolytic oxidation." Surface and Coatings
Technology 223 (2013): 47-51.*

English Abstract and English Machine Translation of Boveri (DE
3842300 A1) (Jun. 21, 1990).*

* cited by examiner

Primary Examiner — Jesse R Roe

(74) *Attorney, Agent, or Firm* — Laurence A. Greenberg;
Werner H. Stemer; Ralph E. Locher

(57) **ABSTRACT**

An adhesion promoter layer is produced by a novel com-
position with a lower cobalt content in an MCrAlY alloy.
The adhesion promoter layer leads to a very slow growth of
the TGO. The nickel-based alloy contains at least (in wt. %):
cobalt (Co) 0.2%-5.0%, chromium (Cr) 14.0%-20.0%; alu-
minum (Al) 6.0%-8.0%; tantalum (Ta) 1.0%-3.0%; yttrium
(Y) 0.3%-0.6%; nickel (Ni) 70.0%-75.0%.

16 Claims, No Drawings

1

ALLOY, POWDER, DUCTILE GAMMA' ADHESION PROMOTER LAYER AND COMPONENT

CROSS-REFERENCE TO RELATED APPLICATION

This application is a divisional of patent application Ser. No. 18/251,916, filed May 5, 2023, now U.S. Pat. No. 12,129,530, which was a § 371 national stage filing of international application PCT/EP2021/077444, filed Oct. 5, 2021, which designated the United States, this application also claims the priority, under 35 U.S.C § 119, of German patent application DE 10 2020 918.0, filed Nov. 5, 2020; the prior applications are herewith incorporated by reference in their entirety.

FIELD AND BACKGROUND OF THE INVENTION

The invention relates to an alloy, to a powder, to a ductile adhesion promoter layer, and to a component.

The thermomechanical behavior of metallic adhesion promoter layers on substrates has a direct influence on the performance of ceramic thermal barrier coating systems which in the case of turbine components comprise a nickel- or cobalt-based substrate, the adhesion promoter layer, and at least one ceramic layer (TBC) over it.

These metallic adhesion promoter layers have a number of strict criteria to meet, such as protection from oxidation, long-term thermal stability, strength, and ductility.

Particularly for hydrogen turbines, the thermal barrier coating system is subject to a different requirement.

SUMMARY OF THE INVENTION

It is therefore an object of the invention to solve the problem stated above.

The object is achieved by an alloy as claimed in the independent alloy claim, a powder as claimed in the independent powder claim, a layer as claimed in the independent layer claim, and a component as claimed in the independent component claim.

The dependent claims list further advantageous measures, which may be combined with one another as desired in order to achieve further advantages.

The invention comprises a nickel-based alloy, more particularly consisting of (in wt %):

cobalt (Co)	0.2%-5.0%, more particularly 1.0%-4%;
chromium (Cr)	14.0%-20.0%, more particularly 16.0%-18.0%;
aluminum (Al)	6.0%-8.0%, more particularly 7.0%;
tantalum (Ta)	1.0%-3.0%, more particularly 2.0%;
yttrium (Y)	0.3%-0.6%;
nickel (Ni)	64.0%-79.0%, more particularly 70.0%-75.0%.

Notable and necessary is the low cobalt (Co) content.

Impurities are always present in the alloy.

The γ' -containing adhesion promoter layer slows down the growth of the aluminum oxide layer (TGO) and is able as a result to improve the thermal-cyclical lifetime of an overlying ceramic layer (TBC) or coating system (substrate+ NiCoCrAl+optionally TBC).

2

A powder composed of the alloy may optionally comprise binders of other particles such as, in particular, ceramic or refractory particles.

A component, more particularly for a hydrogen-driven gas turbine, comprises a substrate.

The substrate preferably comprises a nickel- or cobalt-based alloy.

Applied atop this is the alloy of the invention, based on NiCoCrAlYTa.

This may be done by means of methods from the prior art, more particularly by means of HVOF and APS.

Likewise conceivable are two-layer NiCoCrAlY protective coats, in which the alloy of the invention preferably forms the outer part.

A TGO forms on this system in operation or as early as during ceramic coating.

A ceramic coating (TBC) on the NiCoCrAlYTa may have a one-layer or two-layer configuration.

Stabilized zirconium oxide preferably constitutes the basis for the TBC.

The invention claimed is:

1. A component, comprising:

a substrate;

a metallic layer formed from a nickel-based alloy or a powder, said nickel-based alloy or said powder each containing (in wt %):

cobalt (Co)	0.2%-5.0%;
chromium (Cr)	14.0%-20.0%;
aluminum (Al)	6.0%-8.0%;
tantalum (Ta)	1.0%-3.0%;
yttrium (Y)	0.3%-0.6%; and
nickel (Ni)	64.0%-79.0%.

a ceramic thermal barrier layer disposed on said metallic layer.

2. The component according to claim 1, wherein said ceramic thermal barrier layer is based on zirconium oxide.

3. The component according to claim 1, wherein said chromium (Cr) is 14% to 16% (in wt %).

4. The component according to claim 1, wherein said chromium (Cr) is 16% to 18% (in wt %).

5. The component according to claim 1, wherein said chromium (Cr) is 18% to 20 (in wt %).

6. The component according to claim 1, wherein the component is configured for hydrogen-driven gas turbines.

7. The component according to claim 1, wherein said substrate is composed of a nickel-based alloy or a cobalt-based alloy.

8. A component, comprising:

a substrate; and

a metallic layer formed from a nickel-based alloy or a powder, said nickel-based alloy or said powder each consisting of (in wt %):

cobalt (Co)	0.2%-5.0%;
chromium (Cr)	14.0%-20.0%;
aluminum (Al)	6.0%-8.0%;
tantalum (Ta)	2.0%;
yttrium (Y)	0.3%-0.6%; and
nickel (Ni)	64.0%-79.0%.

9. The component according to claim 8, further comprising a ceramic thermal barrier layer.

10. The component according to claim 9, wherein said ceramic thermal barrier layer is based on zirconium oxide.

11. The component according to claim 8, wherein said chromium (Cr) is 14% to 16% (in wt %).

12. The component according to claim 8, wherein said chromium (Cr) is 16% to 18% (in wt %).

13. The component according to claim 8, wherein said chromium (Cr) is 18% to 20 (in wt %).

14. The component according to claim 8, wherein the component is configured for hydrogen-driven gas turbines.

15. The component according to claim 9, wherein said ceramic thermal barrier layer is disposed on said metallic layer.

16. The component according to claim 8, wherein said substrate is composed of a nickel-based alloy or a cobalt-based alloy.

* * * * *