US012392064B2

(12) **United States Patent**
Lecuivre

(10) **Patent No.:** US 12,392,064 B2
(45) **Date of Patent:** Aug. 19, 2025

(54) **PROSTHETIC POROUS KNIT**

(71) Applicant: **SOFRADIM PRODUCTION**, Trevoux (FR)

(72) Inventor: **Julie Lecuivre**, Jassans-Riottier (FR)

(73) Assignee: **SOFRADIM PRODUCTION**, Trevoux (FR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **18/886,956**

(22) Filed: **Sep. 16, 2024**

(65) **Prior Publication Data**

US 2025/0003123 A1   Jan. 2, 2025

Related U.S. Application Data

(63) Continuation of application No. 18/219,317, filed on Jul. 7, 2023, now Pat. No. 12,091,788, which is a (Continued)

(30) **Foreign Application Priority Data**

Dec. 5, 2014   (EP) 14306956

(51) **Int. Cl.**
D04B 21/12   (2006.01)
A61F 2/00   (2006.01)

(52) **U.S. Cl.**
CPC **D04B 21/12** (2013.01); **A61F 2/0063** (2013.01); **A61F 2002/0068** (2013.01); **A61F 2240/001** (2013.01); **D10B 2509/08** (2013.01)

(58) **Field of Classification Search**
CPC D04B 21/10; D04B 21/12; D04B 21/20; D04B 21/22; A61F 2/0063;
(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

1,187,158 A   6/1916   Mcginley
3,118,294 A   1/1964   Van Laethem
(Continued)

FOREIGN PATENT DOCUMENTS

CA   1317836 C   5/1993
CN   103533910 A   1/2014
(Continued)

OTHER PUBLICATIONS

Amid, P., "Lichtenstein tension-free hernioplasty: Its inception, evolution, and principles," Hernia, 2004; pp. 1-7, 8, published online Sep. 2003.
(Continued)

Primary Examiner — Danny Worrell
(74) *Attorney, Agent, or Firm* — Weber Rosselli & Cannon LLP

(57)   **ABSTRACT**

The invention relates to a prosthetic porous knit based on a monofilament of a biocompatible polymer material, the pattern followed for the knitting of said monofilament on a warp knitting machine having two guide bars B1, B2 being the following, according to the ISO 11676 standard:
    Bar B1: 1.2/4.5/4.3/4.5/4.3/1.0/1.2/1.0//
    Bar B2: 4.3/1.0/1.2/1.0/1.2/4.5/4.3/4.5//
The invention further relates to a method for producing such a knit and to a hernia prosthesis comprising such a knit.

19 Claims, 4 Drawing Sheets

Related U.S. Application Data

continuation of application No. 17/840,376, filed on Jun. 14, 2022, now Pat. No. 11,713,526, which is a continuation of application No. 16/995,763, filed on Aug. 17, 2020, now Pat. No. 11,359,313, which is a continuation of application No. 15/920,577, filed on Mar. 14, 2018, now Pat. No. 10,745,835, which is a continuation of application No. 14/928,082, filed on Oct. 30, 2015, now Pat. No. 9,932,695.

(58) **Field of Classification Search**
CPC A61F 2002/0068; A61F 2240/001; D10B 2509/08
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,124,136 A	3/1964	Usher
3,272,204 A	9/1966	Artandi et al.
3,276,448 A	10/1966	Kronenthal
3,320,649 A	5/1967	Naimer
3,364,200 A	1/1968	Ashton et al.
3,570,482 A	3/1971	Shigeru et al.
4,006,747 A	2/1977	Kronenthal et al.
4,060,081 A	11/1977	Yannas et al.
4,173,131 A	11/1979	Melton et al.
4,193,137 A	3/1980	Heck
4,248,064 A	2/1981	Odham
4,294,241 A	10/1981	Miyata
4,307,717 A	12/1981	Hymes et al.
4,338,800 A	7/1982	Matsuda
4,476,697 A	10/1984	Schafer et al.
4,487,865 A	12/1984	Balazs et al.
4,500,676 A	2/1985	Balazs et al.
4,511,653 A	4/1985	Play et al.
4,527,404 A	7/1985	Nakagaki et al.
4,591,501 A	5/1986	Cioca
4,597,762 A	7/1986	Walter et al.
4,603,695 A	8/1986	Ikada et al.
4,631,932 A	12/1986	Sommers
4,670,014 A	6/1987	Huc et al.
4,709,562 A	12/1987	Matsuda
4,748,078 A	5/1988	Doi et al.
4,759,354 A	7/1988	Quarfoot
4,769,038 A	9/1988	Bendavid et al.
4,796,603 A	1/1989	Dahlke et al.
4,813,942 A	3/1989	Alvarez
4,841,962 A	6/1989	Berg et al.
4,854,316 A	8/1989	Davis
4,925,294 A	5/1990	Geshwind et al.
4,931,546 A	6/1990	Tardy et al.
4,942,875 A	7/1990	Hlavacek et al.
4,948,540 A	8/1990	Nigam
4,950,483 A	8/1990	Ksander et al.
4,970,298 A	11/1990	Silver et al.
5,002,551 A	3/1991	Linsky et al.
5,147,374 A	9/1992	Fernandez
5,162,430 A	11/1992	Rhee et al.
5,171,273 A	12/1992	Silver et al.
5,176,692 A	1/1993	Wilk et al.
5,192,301 A	3/1993	Kamiya et al.
5,196,185 A	3/1993	Silver et al.
5,201,745 A	4/1993	Tayot et al.
5,201,764 A	4/1993	Kelman et al.
5,206,028 A	4/1993	Li
5,217,493 A	6/1993	Raad et al.
5,254,133 A	10/1993	Seid
5,256,418 A	10/1993	Kemp et al.
5,263,983 A	11/1993	Yoshizato et al.
5,304,595 A	4/1994	Rhee et al.
5,306,500 A	4/1994	Rhee et al.
5,324,775 A	6/1994	Rhee et al.
5,328,955 A	7/1994	Rhee et al.
5,334,527 A	8/1994	Brysk
5,339,657 A	8/1994	Mcmurray
5,350,583 A	9/1994	Yoshizato et al.
5,356,432 A	10/1994	Rutkow et al.
5,368,549 A	11/1994	Mcvicker
5,376,375 A	12/1994	Rhee et al.
5,376,376 A	12/1994	Li
5,397,331 A	3/1995	Himpens et al.
5,399,361 A	3/1995	Song et al.
5,413,791 A	5/1995	Rhee et al.
5,425,740 A	6/1995	Hutchinson, Jr.
5,428,022 A	6/1995	Palefsky et al.
5,433,996 A	7/1995	Kranzler et al.
5,441,491 A	8/1995	Verschoor et al.
5,441,508 A	8/1995	Gazielly et al.
5,456,693 A	10/1995	Conston et al.
5,456,711 A	10/1995	Hudson
5,466,462 A	11/1995	Rosenthal et al.
5,480,644 A	1/1996	Freed
5,487,895 A	1/1996	Dapper et al.
5,490,984 A	2/1996	Freed
5,512,291 A	4/1996	Li
5,512,301 A	4/1996	Song et al.
5,514,181 A	5/1996	Light et al.
5,522,840 A	6/1996	Krajicek
5,523,348 A	6/1996	Rhee et al.
5,536,656 A	7/1996	Kemp et al.
5,543,441 A	8/1996	Rhee et al.
5,565,210 A	10/1996	Rosenthal et al.
5,567,806 A	10/1996	Abdul-Malak et al.
5,569,273 A	10/1996	Titone et al.
RE35,399 E	12/1996	Eisenberg
5,593,441 A	1/1997	Lichtenstein et al.
5,595,621 A	1/1997	Light et al.
5,601,571 A	2/1997	Moss
5,607,474 A	3/1997	Athanasiou et al.
5,607,590 A	3/1997	Shimizu
5,614,587 A	3/1997	Rhee et al.
5,618,551 A	4/1997	Tardy et al.
5,634,931 A	6/1997	Kugel
5,639,796 A	6/1997	Lee
5,665,391 A	9/1997	Lea
5,667,839 A	9/1997	Berg
5,681,568 A	10/1997	Goldin et al.
5,686,115 A	11/1997	Vournakis et al.
5,690,675 A	11/1997	Sawyer et al.
5,695,525 A	12/1997	Mulhauser et al.
5,697,978 A	12/1997	Sgro
5,700,476 A	12/1997	Rosenthal et al.
5,700,477 A	12/1997	Rosenthal et al.
5,709,934 A	1/1998	Bell et al.
5,716,409 A	2/1998	Debbas
5,720,981 A	2/1998	Eisinger
5,732,572 A	3/1998	Litton
5,749,895 A	5/1998	Sawyer et al.
5,752,974 A	5/1998	Rhee et al.
5,766,246 A	6/1998	Mulhauser et al.
5,766,631 A	6/1998	Arnold
5,769,864 A	6/1998	Kugel
5,771,716 A	6/1998	Schlussel
5,785,983 A	7/1998	Furlan et al.
5,800,541 A	9/1998	Rhee et al.
5,814,328 A	9/1998	Gunasekaran
5,833,705 A	11/1998	Ken et al.
5,840,011 A	11/1998	Landgrebe et al.
5,861,034 A	1/1999	Taira et al.
5,863,984 A	1/1999	Doillon et al.
5,869,080 A	2/1999	Mcgregor et al.
5,871,767 A	2/1999	Dionne et al.
5,876,444 A	3/1999	Lai
5,891,558 A	4/1999	Bell et al.
5,899,909 A	5/1999	Claren et al.
5,906,937 A	5/1999	Sugiyama et al.
5,910,149 A	6/1999	Kuzmak
5,911,731 A	6/1999	Pham et al.
5,916,225 A	6/1999	Kugel
5,919,232 A	7/1999	Chaffringeon et al.
5,919,233 A	7/1999	Knopf et al.
5,922,026 A	7/1999	Chin
5,931,165 A	8/1999	Reich et al.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,942,278 A	8/1999	Hagedorn et al.
5,962,136 A	10/1999	Dewez et al.
5,972,022 A	10/1999	Huxel
RE36,370 E	11/1999	Li
5,993,844 A	11/1999	Abraham et al.
5,994,325 A	11/1999	Roufa et al.
5,997,895 A	12/1999	Narotam et al.
6,001,895 A	12/1999	Harvey et al.
6,008,292 A	12/1999	Lee et al.
6,015,844 A	1/2000	Harvey et al.
6,039,686 A	3/2000	Robert
6,042,534 A	3/2000	Gellman et al.
6,042,592 A	3/2000	Schmitt
6,043,089 A	3/2000	Sugiyama et al.
6,051,425 A	4/2000	Morota et al.
6,056,688 A	5/2000	Benderev et al.
6,056,970 A	5/2000	Greenawalt et al.
6,057,148 A	5/2000	Sugiyama et al.
6,063,396 A	5/2000	Kelleher
6,066,776 A	5/2000	Goodwin et al.
6,066,777 A	5/2000	Benchetrit
6,071,292 A	6/2000	Makower et al.
6,077,281 A	6/2000	Das
6,080,194 A	6/2000	Pachence et al.
6,083,522 A	7/2000	Chu et al.
6,120,539 A	9/2000	Eldridge et al.
6,132,765 A	10/2000	Dicosmo et al.
6,143,037 A	11/2000	Goldstein et al.
6,153,292 A	11/2000	Bell et al.
6,165,488 A	12/2000	Tardy et al.
6,171,318 B1	1/2001	Kugel et al.
6,174,320 B1	1/2001	Kugel et al.
6,176,863 B1	1/2001	Kugel et al.
6,179,872 B1	1/2001	Bell et al.
6,197,325 B1	3/2001	Macphee et al.
6,197,934 B1	3/2001	Devore et al.
6,197,935 B1	3/2001	Doillon et al.
6,210,439 B1	4/2001	Firmin et al.
6,221,109 B1	4/2001	Geistlich et al.
6,224,616 B1	5/2001	Kugel
6,241,768 B1	6/2001	Agarwal et al.
6,258,124 B1	7/2001	Darois et al.
6,262,332 B1	7/2001	Ketharanathan
6,264,702 B1	7/2001	Ory et al.
6,267,772 B1	7/2001	Mulhauser et al.
6,277,397 B1	8/2001	Shimizu
6,280,453 B1	8/2001	Kugel et al.
6,287,316 B1	9/2001	Agarwal et al.
6,290,708 B1	9/2001	Kugel et al.
6,306,424 B1	10/2001	Vyakarnam et al.
6,312,474 B1	11/2001	Francis et al.
6,328,686 B1	12/2001	Robert
6,334,872 B1	1/2002	Termin et al.
6,383,201 B1	5/2002	Dong
6,391,333 B1	5/2002	Li et al.
6,391,939 B2	5/2002	Tayot et al.
6,408,656 B1	6/2002	Ory et al.
6,410,044 B1	6/2002	Chudzik et al.
6,413,742 B1	7/2002	Olsen et al.
6,428,978 B1	8/2002	Olsen et al.
6,436,030 B2	8/2002	Rehil
6,440,167 B2	8/2002	Shimizu
6,443,964 B1	9/2002	Ory et al.
6,447,551 B1	9/2002	Goldmann
6,447,802 B2	9/2002	Sessions et al.
6,448,378 B2	9/2002	Devore et al.
6,451,032 B1	9/2002	Ory et al.
6,451,301 B1	9/2002	Sessions et al.
6,454,787 B1	9/2002	Maddalo et al.
6,477,865 B1	11/2002	Matsumoto
6,479,072 B1	11/2002	Morgan et al.
6,500,464 B2	12/2002	Ceres et al.
6,509,031 B1	1/2003	Miller et al.
6,511,958 B1	1/2003	Atkinson et al.
6,514,286 B1	2/2003	Leatherbury et al.
6,514,514 B1	2/2003	Atkinson et al.
6,540,773 B2	4/2003	Dong
6,541,023 B1	4/2003	Andre et al.
6,548,077 B1	4/2003	Gunasekaran
6,554,855 B1	4/2003	Dong
6,559,119 B1	5/2003	Burgess et al.
6,566,345 B2	5/2003	Miller et al.
6,575,988 B2	6/2003	Rousseau
6,576,019 B1	6/2003	Atala
6,596,002 B2	7/2003	Therin et al.
6,596,304 B1	7/2003	Bayon et al.
6,599,323 B2	7/2003	Melican et al.
6,599,524 B2	7/2003	Li et al.
6,599,690 B1	7/2003	Abraham et al.
6,613,348 B1	9/2003	Jain
6,623,963 B1	9/2003	Mueller et al.
6,630,414 B1	10/2003	Matsumoto
6,638,284 B1	10/2003	Rousseau et al.
6,652,594 B2	11/2003	Francis et al.
6,653,450 B1	11/2003	Berg et al.
6,656,206 B2	12/2003	Corcoran et al.
6,660,280 B1	12/2003	Allard et al.
6,669,735 B1	12/2003	Pelissier
6,682,760 B2	1/2004	Noff et al.
6,685,714 B2	2/2004	Rousseau
6,706,684 B1	3/2004	Bayon et al.
6,706,690 B2	3/2004	Reich et al.
6,719,795 B1	4/2004	Bryan et al.
6,723,335 B1	4/2004	Moehlenbruck et al.
6,730,299 B1	5/2004	Tayot et al.
6,743,435 B2	6/2004	Devore et al.
6,755,868 B2	6/2004	Rousseau
6,773,723 B1	8/2004	Spiro et al.
6,790,213 B2	9/2004	Cherok et al.
6,790,454 B1	9/2004	Abdul et al.
6,800,082 B2	10/2004	Rousseau
6,833,408 B2	12/2004	Sehl et al.
6,835,336 B2	12/2004	Watt
6,852,330 B2	2/2005	Bowman et al.
6,869,938 B1	3/2005	Schwartz et al.
6,893,653 B2	5/2005	Abraham et al.
6,896,904 B2	5/2005	Spiro et al.
6,936,276 B2	8/2005	Spiro et al.
6,939,562 B2	9/2005	Spiro et al.
6,949,625 B2	9/2005	Tayot
6,966,918 B1	11/2005	Schuldt-Hempe et al.
6,971,252 B2	12/2005	Therin et al.
6,974,679 B2	12/2005	Andre et al.
6,974,862 B2	12/2005	Ringeisen et al.
6,977,231 B1	12/2005	Matsuda
6,988,386 B1	1/2006	Okawa et al.
7,025,063 B2	4/2006	Snitkin et al.
7,041,868 B2	5/2006	Greene et al.
RE39,172 E	7/2006	Bayon et al.
7,098,315 B2	8/2006	Schaufler
7,175,852 B2	2/2007	Simmoteit et al.
7,192,604 B2	3/2007	Brown et al.
7,207,962 B2	4/2007	Anand et al.
7,214,765 B2	5/2007	Ringeisen et al.
7,226,611 B2	6/2007	Yura et al.
7,229,453 B2	6/2007	Anderson et al.
7,594,921 B2	9/2009	Browning
7,614,258 B2	11/2009	Cherok et al.
7,670,380 B2	3/2010	Cauthen, III et al.
8,418,508 B2	4/2013	Lecuivre et al.
9,308,070 B2	4/2016	Mortarino et al.
9,932,695 B2	4/2018	Lecuivre et al.
10,745,835 B2	8/2020	Lecuivre
11,359,313 B2	6/2022	Lecuivre
11,713,526 B2	8/2023	Lecuivre
12,091,788 B2*	9/2024	Lecuivre A61F 2/0063
2001/0008930 A1	7/2001	Tayot et al.
2002/0095218 A1	7/2002	Carr et al.
2002/0116070 A1	8/2002	Amara et al.
2003/0013989 A1	1/2003	Obermiller et al.
2003/0023316 A1	1/2003	Brown et al.
2003/0086975 A1	5/2003	Ringeisen
2003/0100954 A1	5/2003	Schuldt-Hempe et al.
2003/0114937 A1	6/2003	Leatherbury et al.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2003/0133967 A1	7/2003	Ruszczak et al.
2003/0212460 A1	11/2003	Darois et al.
2003/0225355 A1	12/2003	Butler
2003/0232746 A1	12/2003	Lamberti et al.
2004/0034373 A1	2/2004	Schuldt-Hempe et al.
2004/0054406 A1	3/2004	Dubson et al.
2004/0059356 A1	3/2004	Gingras
2004/0101546 A1	5/2004	Gorman et al.
2004/0138762 A1	7/2004	Therin et al.
2004/0172048 A1	9/2004	Browning
2004/0215219 A1	10/2004	Eldridge et al.
2005/0002893 A1	1/2005	Goldmann
2005/0010306 A1	1/2005	Priewe et al.
2005/0021058 A1	1/2005	Negro
2005/0085924 A1	4/2005	Darois et al.
2005/0113849 A1	5/2005	Popadiuk et al.
2005/0113938 A1	5/2005	Jamiolkowski et al.
2005/0137512 A1	6/2005	Campbell et al.
2005/0142161 A1	6/2005	Freeman et al.
2005/0148963 A1	7/2005	Brennan
2005/0175659 A1	8/2005	Macomber et al.
2005/0228408 A1	10/2005	Fricke et al.
2005/0232979 A1	10/2005	Shoshan
2005/0244455 A1	11/2005	Greenawalt
2005/0267521 A1	12/2005	Forsberg
2005/0288691 A1	12/2005	Leiboff
2006/0094318 A1	5/2006	Matsuda et al.
2006/0135921 A1	6/2006	Wiercinski et al.
2006/0147501 A1	7/2006	Hillas et al.
2006/0167561 A1	7/2006	Odar et al.
2006/0216320 A1	9/2006	Kitazono et al.
2006/0252981 A1	11/2006	Matsuda et al.
2007/0031474 A1	2/2007	Tayot et al.
2007/0161109 A1	7/2007	Archibald et al.
2007/0280990 A1	12/2007	Stopek
2007/0297987 A1	12/2007	Stad et al.
2007/0299538 A1	12/2007	Roeber
2008/0147198 A1	6/2008	Cherok et al.
2010/0016872 A1	1/2010	Bayon et al.
2010/0191088 A1	7/2010	Anderson et al.
2011/0295565 A1	12/2011	Ozen
2012/0198894 A1	8/2012	Lecuivre et al.

FOREIGN PATENT DOCUMENTS

CN	103534397 A	1/2014
CN	105147416 A	12/2015
DE	19544162 C1	4/1997
DE	10019604 A1	10/2001
DE	10043396 C1	6/2002
EP	0194192 A1	9/1986
EP	0248544 A1	12/1987
EP	0276890 A2	8/1988
EP	0372969 A1	6/1990
EP	0544485 A1	6/1993
EP	0552576 A1	7/1993
EP	0614650 A2	9/1994
EP	0621014 A1	10/1994
EP	0625891 A1	11/1994
EP	0637452 A1	2/1995
EP	0705878 A2	4/1996
EP	0719527 A1	7/1996
EP	0774240 A1	5/1997
EP	0797962 A2	10/1997
EP	0827724 A2	3/1998
EP	0836838 A1	4/1998
EP	0895762 A2	2/1999
EP	0898944 A2	3/1999
EP	1017415 A1	7/2000
EP	1052319 A1	11/2000
EP	1055757 A1	11/2000
EP	1216717 A1	6/2002
EP	1216718 A1	6/2002
EP	0693523 B1	11/2002
EP	1315468 A2	6/2003
EP	1382728 A1	1/2004
EP	1484070 A1	12/2004
EP	1561480 A2	8/2005
EP	1782848 A2	5/2007
FR	2244853 A1	4/1975
FR	2257262 A1	8/1975
FR	2308349 A1	11/1976
FR	2453231 A1	10/1980
FR	2715405 A1	7/1995
FR	2724563 A1	3/1996
FR	2744906 A1	8/1997
FR	2766698 A1	2/1999
FR	2771622 A1	6/1999
FR	2779937 A1	12/1999
FR	2859624 B1	12/2005
FR	2863277 B1	6/2006
FR	2884706 B1	4/2008
GB	2051153 A	1/1981
JP	H0332677 U	3/1991
JP	H05237128 A	9/1993
JP	H09137380 A	5/1997
JP	2002518129 A	6/2002
JP	2011505220 A	2/2011
WO	8902445 A1	3/1989
WO	8908467 A1	9/1989
WO	9012551 A1	11/1990
WO	9206639 A2	4/1992
WO	9207648 A2	5/1992
WO	9220349 A1	11/1992
WO	9302168 A1	2/1993
WO	9311805 A1	6/1993
WO	9318174 A1	9/1993
WO	9417747 A1	8/1994
WO	9507666 A1	3/1995
WO	9518638 A1	7/1995
WO	9532687 A1	12/1995
WO	9603091 A1	2/1996
WO	9608277 A1	3/1996
WO	9609795 A1	4/1996
WO	9614805 A1	5/1996
WO	9641588 A1	12/1996
WO	9702789 A1	1/1997
WO	9735533 A1	10/1997
WO	9835632 A1	8/1998
WO	9849967 A1	11/1998
WO	9905990 A1	2/1999
WO	9906079 A1	2/1999
WO	9906080 A1	2/1999
WO	9951163 A1	10/1999
WO	0016821 A1	3/2000
WO	0067663 A1	11/2000
WO	0115625 A1	3/2001
WO	0180773 A1	11/2001
WO	02078568 A1	10/2002
WO	2004004600 A1	1/2004
WO	2004071349 A2	8/2004
WO	2004078120 A2	9/2004
WO	2004103212 A1	12/2004
WO	2005011280 A1	2/2005
WO	2005013863 A2	2/2005
WO	2005018698 A1	3/2005
WO	2005105172 A1	11/2005
WO	2006018552 A1	2/2006
WO	2006023444 A2	3/2006
WO	2007048099 A3	9/2010
WO	2011042811 A2	4/2011
WO	2012123582 A1	9/2012

OTHER PUBLICATIONS

Blondin, C. et al., "Inhibition of Complement Activation by Natural Sulfated Polysaccharides (Fucans) from Brown Seaweed," Molecular Immuol., Mar. 1994, pp. 247-253, 31(4).

Blondin, C. et al., "Relationships between chemical characteristics and anticomplementary activity of fucans," Biomaterials, Mar. 1996, pp. 597-603, 17(6).

(56)　　　　　**References Cited**

OTHER PUBLICATIONS

Boisson-Vidal, C. et al., "Neoangiogenesis Induced by Progenitor Endothelial Cells: Effect of Fucoidan From Marine Algae," Cardiovascular & Hematological Agents in Medicinal Chem., Jan. 2007, pp. 67-77, 5(1).

Bracco, P. et al., "Comparison of polypropylene and polyethylene terephthalate (Dacron) meshes for abdominal wall hernia repair: A chemical and morphological study," Hernia, 2005, pp. 51-55, 9 (1), published online Sep. 2004.

Canadian Office Action issued in Canadian Patent application No. 2,911,337 dated Oct. 12, 2021.

Collins, R. et al., "Use of collagen film as a dural substitute: Preliminary animal studies," Journal of Biomedical Materials Research, Feb. 1991, pp. 267-276, vol. 25.

Ellouali, M. et al., "Antitumor Activity of Low Molecular Weight Fucans Extracted from Brown Seaweed *Ascophyllum nodosum*," Anticancer Res., Nov.-Dec. 1993, pp. 2011-2020, 12 (6A).

European Search Report for EP 14306956.5 date of completion is May 20, 2015 (4 pages).

Examination Report No. 1 issued in Australian Patent Application No. 2020200947 dated Oct. 29, 2020, 3 pages.

Examination Report No. 1 issued is Australian Patent Application No. 2015249131 dated Jul. 5, 2019, 4 pages.

Haneji, K et al., "Fucoidan extracted from Cladosiphon Okamuranus Tokida Induces Apoptosis of Human T-cell Leukemia Virus Type 1-Infected T-Cell Lines and Primary Adult T-Cell Leukemia Cells," Nutrition and Cancer, 2005, pp. 189-201, 52(2), published online Nov. 2009.

Haroun-Bouhedja, F. et al., “In Vitro Effects of Fucans on MDA-MB231 Tumor Cell Adhesion and Invasion, Anticancer Res., Jul.-Aug. 2002, pp. 2285-2292, 22(4).

Haroun-Bouhedja, F. et al., "Relationship between sulfate groups and biological activities of fucans," Thrombosis Res., Dec. 2000, pp. 453-459, 100(5).

Hirano, S. et al., "The blood biocompatibility of chitosan and N-acylchitosans," J. Biomed. Mater. Res., Apr. 1985, 413-417, 19.

Japanese Office Action issued in JP Patent Application No. 2015-230410 dated Jul. 26, 2019 with English translation, 5 pages.

Junge, K. et al., "Functional and Morphologic Properties of a Modified Mesh for Inguinal Hernia Repair," World J. Surg., Sep. 2002, pp. 1472-1480, 26.

Kanabar, V. et al., "Some structural determinants of the antiproliferative effect of heparin-like molecules on human airway smooth muscle," Br. J. Pharmacol., Oct. 2005, pp. 370-777, 146(3).

Klinge, U. et al., "Foreign Body Reaction to Meshes Used for the Repair of Abdominal Wall Hernias," Eur J. Surg, Sep. 1999, pp. 665-673, 165.

Klinge, U. et al., "Functional and Morphological Evaluation of a Low-Weight, Monofilament Polypropylene Mesh for Hernia Repair," J. Biomed. Mater. Res., Jan. 2002, pp. 129-136, 63.

Langenbech, M. R. et al., "Comparison of biomaterials in the early postoperative period," Surg Enclose., May 2003, pp. 1105-1109, 17 (7).

Logeart, D. et al., "Fucans, sulfated polysaccharides extracted from brown seaweeds, inhibit vascular smooth muscle cell proliferation. II. Degradation and molecular weight effect," Eur. J. Cell. Biol., Dec. 1997, pp. 385-390, 74(4).

Malette, W. G. et al., "Chitosan, A New Hemostatic," Ann Th. Surg., Jul. 1983, pp. 55-58, 36.

Muzzarelli, R. et al., "Reconstruction of parodontal tissue with chitosan," Biomaterials, Nov. 1989, pp. 598-604, 10.

Notice of Allowance issued in Japanese patent application No. 2015-230410 dated Dec. 3, 2019; with English translation; 5 pages.

Notification of Second Office Action issued in Chinese Application No. 201910285263.4 dated May 6, 2021, with English translation.

Notification of the First Office Action issued in Chinese Application No. 201710183803.9 dated Aug. 28, 2020, 34 pages.

Notification of the First Office Action issued in Chinese Patent Application No. 201910285263.4 dated Sep. 1, 2020, 14 pages.

O'Dwyer, P. et al., "Randomized clinical trial assessing impact of a lightweight or heavyweight mesh on chronic pain after inguinal hernia repair," Br. J. Surg., Feb. 2005, pp. 166-170, 92(2).

Preliminary Search Report from French Patent Office dated Dec. 20, 2006, 3 pages.

Prokop, A. et al., "Water Soluble Polymers for Immunoisolation I: Complex Coacevation and Cytotoxicity," Advances in Polymer Science, Jul. 1998, pp. 1-51, 136.

Rao, B. et al., "Use of chitosan as a biomaterial: Studies on its safety and hemostatic potential," J. Biomed. Mater. Res., Jan. 1997, pp. 21-28, 34.

Rosen, M. et al., "Laparoscopic component separation in the single-stage treatment of infected abdominal wall prosthetic removal," Hernia, 2007, pp. 435-440, 11, published online Jul. 2007.

Scheidbach, H. et al., "In vivo studies comparing the biocompatibility of various polypropylene meshes and their handling properties during endoscopic total extraperitoneal (TEP) patchplasty: An experimental study in pigs," Surg. Endosc., Feb. 2004, pp. 211-220,18(2).

Strand, S. et al., "Screening of Chitosans and Conditions for Bacterial Flocculation," Biomacromolecules, Mar. 2001, 126-133, 2.

T Muhl. et al., "New Objective Measurement to Characterize the Porosity of Textile Implants," Wiley Interscience, Journal of Biomedical Materials ResearchPart B: Applied Biomaterials, May 11, 2007, p. 176-183.

Varum, K. et al., "In vitro degradation rates of partially N-acetylated chitosans in human serum," Carbohydrate Research, Mar. 1997, pp. 99-101, 299.

Welty, G. et al., "Functional impairment and complaints following incisional hernia repair with different polypropylene meshes," Hernia, Aug. 2001; pp. 142-147, 5.

Zvyagintseva, T. et al., "Inhibition of complement activation by water-soluble polysaccharides of some far-eastern brown seaweeds," Comparative Biochem and Physiol, Jul. 2000, pp. 209-215, 126(3).

* cited by examiner

FIG. 1

FIG. 2

FIG. 3

**FIG. 4**

FIG. 5

FIG. 6

FIG. 7

FIG. 8

FIG. 9

FIG. 10

PROSTHETIC POROUS KNIT

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of U.S. patent application Ser. No. 18/219,317 filed Jul. 7, 2023, which is a continuation of U.S. patent application Ser. No. 17/840,376 filed Jun. 14, 2022, which is a continuation of U.S. patent application Ser. No. 16/995,763 filed Aug. 17, 2020, now U.S. Pat. No. 11,359,313, which is a continuation of U.S. patent application Ser. No. 15/920,577 filed Mar. 14, 2018, now U.S. Pat. No. 10,745,835, which is a continuation application of U.S. patent application Ser. No. 14/928,082 filed Oct. 30, 2015, now U.S. Pat. No. 9,932,695, which claims benefit of and priority to European Patent Application No. 14306956 filed Dec. 5, 2014, the disclosures of each of the above-identified applications are hereby incorporated by reference in their entirety.

TECHNICAL FIELD

The present invention relates to a prosthetic porous knit useful in parietal surgery, the knit having a lightweight and macroporous structure while showing good mechanical strength properties.

BACKGROUND

Wall-reinforcing prostheses, for example prostheses for reinforcing the abdominal wall, are widely used in the surgical field. These prostheses are intended to treat hernias by temporarily or permanently filling a tissue defect. These prostheses are generally made of biocompatible prosthetic fabric, in particular prosthetic knits, and can have a number of shapes, for example rectangular, circular or oval, depending on the anatomical structure to which they are to be fitted.

In a view of reducing the foreign material implanted into the body of a patient, it is desired to produce lightweight knits, intended to be used as wall reinforcing prostheses. In addition, for facilitating the work of the surgeon at the time he puts the prosthesis in place at the implantation site, it is further desired that the prosthetic knit show a good transparency. Moreover, the wall reinforcing prosthesis should also favor a good tissue ingrowth. In this view, it is desired that the knit used for wall reinforcing prostheses show a plurality of pores, and preferably large pores.

Lightweight porous knits usable in the manufacture of wall reinforcing prostheses already exist. Nevertheless, they sometimes show poor mechanical strength. Indeed, the knit is generally pliant and soft in order to conform to the abdominal wall and flex with movement of the abdominal wall once implanted. The knit may be held in place by suturing, stapling, or tacking the knit to surrounding biological tissue. In particular, existing lightweight porous knits may show a poor resistance to fracture when they are sutured or tacked to the surrounding biological tissue.

In addition, the performance of the abdominal wall hernia repair using a prosthetic knit fixed on the abdominal wall depends in part upon the shear forces experienced at the knit fixation points. These shear forces may be quite high as a result of high intra-abdominal pressure.

Too high shear forces at knit fixation points, once the knit or prosthesis is implanted and has been fixed for example by sutures at the abdominal wall, may lead to abdominal wall repair recurrences and/or generate pain for the patient. The

distribution of shear forces at fixation points is important to assess the safety and the efficacy of the abdominal wall repair.

SUMMARY

In particular, it would be desirable to provide a prosthesis made from a knit for which the distribution of the shear forces at fixation points is as regular as possible and for which the value of shear forces at fixation points is as low as possible, so that the prosthesis may for example be introduced at the implantation site and implanted without the surgeon having to check for a specific position of the warp or weft direction of the knit. It would further be desirable to provide a prosthesis made from a knit for which the risk of fixation pull out and/or implant failure at fixation points is reduced.

In addition, if a knit is too pliant and soft, it may not resist sufficiently to the intra abdominal pressure during specific movements of the patient, for example when the patient coughs or jumps. The knit may then be prone to undesired bulging phenomenon and may not ensure sufficient reinforcement of the abdominal wall in such conditions.

There is therefore a need for a porous prosthetic knit that would be capable of having a lightweight and macroporous structure while at the same time show good mechanical strength properties.

A first aspect of the invention is a prosthetic porous knit based on a monofilament of a biocompatible polymer material, the pattern followed for the knitting of said monofilament on a knitting machine having two guide bars B1, B2 being the following, according to the ISO 11676 standard:

Bar B1: 1.2/4.5/4.3/4.5/4.3/1.0/1.2/1.0//
Bar B2: 4.3/1.0/1.2/1.0/1.2/4.5/4.3/4.5//

Another aspect of the invention is a method for manufacturing the prosthetic knit above comprising the step of producing a knit with a monofilament of a biocompatible polymer material on a knitting machine having two guide bars B1, B2 according to the following pattern, according to the ISO 11676 standard:

Bar B1: 1.2/4.5/4.3/4.5/4.3/1.0/1.2/1.0//
Bar B2: 4.3/1.0/1.2/1.0/1.2/4.5/4.3/4.5//

Guide bars B1 and B2 may be threaded 1 full 1 empty and may move symmetrically.

The knitting machine may be a warp knitting machine or a raschel knitting machine.

The knit of the invention is porous. In particular, the knit of the invention comprises openings or pores: these openings or pores are in particular generated by the pattern followed for the knitting of the monofilament of the knit according to the invention. The porosity of the knit of the invention confers to the knit a transparency allowing the surgeon to have a good visibility of the implantation site at the time he puts the knit or prosthesis in place.

The knit of the invention is lightweight. The knit of the invention preferably shows a mass per unit area ranging from about 40 to about 70 g/m^2, preferably ranging from about 40 to about 50 g/m^2, and more preferably of about 44 g/m^2, 45 g/m^2, 46 g/m^2, 47 g/m^2 or 48 g/m^2, measured according to ISO 3801:1977 «Determination of mass per unit length and mass per unit area», 5 specimens 1 dm^2. Such a low mass per unit area allows introducing only a little quantity of foreign material in the body of the patient.

The knit of the invention is made from a monofilament of biocompatible polymer material.

The biocompatible polymer may be synthetic or natural. The biocompatible polymer may be biodegradable, non-

biodegradable or a combination of biodegradable and non-biodegradable. The term "biodegradable" as used herein is defined to include both bioabsorbable and bioresorbable materials. By biodegradable, it is meant that the materials decompose, or lose structural integrity under body conditions (e.g., enzymatic degradation or hydrolysis) or are broken down (physically or chemically) under physiologic conditions in the body such that the degradation products are excretable or absorbable by the body.

The biocompatible polymer may be selected from the group consisting of biodegradable polymers, non-biodegradable polymers, and combinations thereof.

In embodiments, the biocompatible polymer material is selected from polypropylene, polyester such as polyethylene terephthalates, polyamide, silicone, polyether ether ketone (PEEK), polyarylether ether ketone (PAEK) polylactic acid (PLA), polycaprolactone (PCL), polydioxanone (PDO), trimethylene carbonate (TMC), polyvinyl alcohol (PVA), polyhydroxyalkanoate (PHA), polyglycolic acid (PGA), copolymers of these materials, and mixtures thereof.

In embodiments, the biocompatible polymer material is polypropylene.

In embodiments, the monofilament has a diameter of from about 0.08 mm to about 0.25 mm, preferably from about 0.10 mm to 0.15 mm, more preferably of about 0.11 mm, 0.12 mm, or 0.13 mm. Such a diameter allows obtaining a good size of the pores and maintaining the lightweight structure of the knit, while maintaining good mechanical properties. In embodiments, the monofilament has a diameter of about 0.12 mm.

In embodiments, the knit comprises a plurality of pores having a diameter above 1 mm. In particular, the plurality of pores having a diameter above 1 mm defines an efficient porosity of said knit ranging from about 35% to about 70%, preferably of about 55%.

By "efficient porosity" is meant according to the present application a porosity taking into account only the pores having a diameter above 1 mm, while leaving out the pores having a diameter less or equal to 1 mm. By "pores having a diameter above 1 mm" is meant the pores which have dimensions greater than 1 mm in all directions. The efficient porosity therefore corresponds to the ratio of the area of the totality of the pores having a diameter above 1 mm as defined above to the area of the totality of the knit studied. The pores having a diameter above 1 mm are measured with a profile projector such as a projector 300V from ORAMA. The "efficient porosity" and its measuring method are described in the publication "*New objective measurements to characterize the porosity of textile implants*", T. Mühl, M. Binnebösel, U. Klinge and T. Goedderz, Journal of Biomedical Materials Research Part B: Applied Biomaterials, p. 176-183.

The efficient porosity as described above is useful for characterizing the ability of the knit to favor cell colonization. Indeed, pores having a diameter above 1 mm are particularly desired for tissue ingrowth after implantation.

The knitting pattern of the knit of the invention defines a plurality of pores having a diameter ranging above 1 mm. The pores may have a substantially hexagonal or circular shape.

In embodiments, the knit of the invention comprises a plurality of pores having a diameter above 2 mm. Such knits with pores having a diameter above 2 mm favor cell colonization and exhibit a good transparency allowing the surgeon to have a better visibility of the surrounding tissues when he puts the knit/prosthesis in place at the implantation site.

In embodiments, the knit of the invention has a tensile breaking strength in the warp direction of at least about 200 N, preferably of about 237 N. In embodiments, the knit of the invention has a tensile breaking strength in the weft direction of at least about 170 N, preferably of about 201 N. In embodiments, the knit of the invention has a bursting strength of at least about 400 kPa, preferably of about 463 kPa. In embodiments, the knit of the invention has a tear strength in the warp direction of at least about 25 N, preferably of about 30 N. In embodiments, the knit of the invention has a tear strength in the weft direction of at least about 25 N, preferably of about 37 N. In embodiments, the knit of the invention has a suture pull out strength in the warp direction of at least about 35 N, preferably of about 46 N. In embodiments, the knit of the invention has a suture pull out strength in the weft direction of at least about 38 N, preferably of about 42 N. In embodiments, the knit of the invention has a tensile strength of at least about 42 N/cm, preferably of about 47 N/cm.

The tensile breaking strength (N), the bursting strength (kPa), the tear strength (N), the suture pull out strength (N) and the tensile strength (N/cm) above are measured according to the methods as indicated in the below Example of the present application.

Following knitting and heat-setting, the knit can be cleaned, packaged and sterilized using conventionally known techniques. The knit of the invention can be used as provided in the package or cut to any desired dimension once removed from the package.

The knit of the invention can be implanted in extraperitoneal site either for inguinal or ventral hernia repair via open or laparoscopic approach. Fixation to the surrounding tissues can be achieved by stapling, conventional sutures or other means.

The prosthetic knit of the invention shows an homogeneous distribution of shear forces at fixation points. In particular, although it is provided with a lightweight structure, the prosthetic knit of the invention shows a good resistance to fracture at fixation points compared to lightweight knits of the prior art.

The knit of the invention may be used on its own as a prosthesis to be implanted into in a patient for hernia repair for example.

Another aspect of the invention is a hernia prosthesis comprising a knit as described above.

BRIEF DESCRIPTION OF THE DRAWINGS

The present invention will become clearer from the following description and from the attached drawings, in which:

FIG. **1** is a schematic view of the knitting pattern of a knit of the invention,

FIG. **2** is a front view of the knit of the invention obtained with the knitting pattern of FIG. **1**,

FIG. **3** is a side view of a schematic configuration of a system for measuring the distribution of the shear forces at fixation points of a knit,

FIG. **4** is an enlarged perspective view of a portion of the system of FIG. **3**.

FIGS. **5** and **6** are schematic views of the form used to obtain the average distribution of shear forces at fixation points, as described in at least one embodiments herein.

FIG. **7** is a schematized graph profile of the shear force distribution of a knit.

FIGS. **8-10** are schematized contour profiles of Knits A, B, and C, respectively.

DETAILED DESCRIPTION

With reference to FIG. **1**, is shown a graphic representing the knitting pattern of the knit of the invention, namely the following pattern according to the ISO 11676 standard:

Bar B1: 1.2/4.5/4.3/4.5/4.3/1.0/1.2/1.0//

Bar B2: 4.3/1.0/1.2/1.0/1.2/4.5/4.3/4.5/

The overall pattern repetition size of the knit of the invention is eight courses. FIG. **1** depicts only one thread from guide bar B1 and one thread from guide bar B2 to better show the movement of the thread. The evolution of the threads at the ninth course is the same as at the first course.

With reference to FIG. **2**, is shown a photograph of the knit **1** of the invention obtained with the knitting pattern as represented in FIG. **1**.

The knit **1** of FIG. **2** was obtained from a monofilament of polypropylene of diameter 0.12 mm.

The knitting pattern of the knit of the invention produces pores greater than about 1.0 mm in diameter. For example, the principal pores **2** of the knit **1** of FIG. **2** have an average size of 2.0×2.4 mm. Such a large size of pores is very favorable for cell colonization and confers to the knit a good transparency allowing a good visibility at the implantation site.

The knit of the invention shows an homogeneous distribution of the shear forces at fixation points. The distribution of the shear forces at fixation points may be evaluated with a system for assessing shear forces distribution at fixation points of textile-based implants, such as an axisymmetrical experimental set-up as described in reference to FIGS. **3** and **4**, such a system allowing exhibiting the capability of a textile to distribute shear forces at fixation points without integrating specific geometrical considerations.

Referring now to FIGS. **3** and **4**, system **10** includes a tissue model **100**, a load simulation device **200**, and an analysis system **300** for assessing characteristics of a textile-based implant **400** when fixed to the tissue model **100** and subjected to a load exerted by the load simulation device **200**. The tissue model **100** includes a base **110** having an upper surface **112** extending along a plane "P" and having a closed outer perimeter **114** that defines an opening **116** therethrough. The upper surface **112** is configured to mimic the inner surface of an abdominal wall: it is flat and horizontal. The opening **116** defined through the upper surface **112** is configured to mimic a defect in an abdominal wall and may be referred to herein as the "defect". The opening **116** has a circular shape and a uniform size and dimension through the height "H" of the base **110**. In the system of FIG. **3**, the opening **116** is an empty circle having a radius of 55 mm with a 10 mm fillet.

The upper surface **112** is covered by a coating **112**a having a coefficient of friction that mimics the frictional coefficient of an inner surface abdominal wall against a textile-based implant **400**. The coefficient of friction is about 0.3.

The base **110** includes a lower planar surface **118** that is stepped down from the upper planar surface **112** at a pre-determined height "H1" and extends around the upper surface **112**.

The base **110** also includes a fixation support under the form of a plurality of rods **120**, configured to secure a textile-based implant **400** thereto at two or more fixation points. The plurality of rods **120** are attached to the lower surface **118** at a predetermined distance "D1" of 20 mm from

each other and a predetermined distance "D2" of 70 mm from the upper surface **112** extremity. The rods **120** are arranged in a simple circle crown fixation, centered to the opening **116**. Each rod **120** includes a first end **120**a fixed to the lower surface **118**, an elongate body **120**b extending from the lower surface **118** towards the upper surface **112** and defining a length "L" of 60 mm, and a second end **120**c terminating about or above the plane "P" defined by the upper surface **112**. The elongate body **120**b extends perpendicularly from the lower surface **118**. The rods **120** are threaded rod M3, with an equivalent radius of 2.5 mm and a Young Modulus of 110 Gpa.

The rods **120** are configured for direct fixation to a portion of the textile-based implant **400** when the textile-based implant **400** is placed upon the upper surface **112** of the tissue model **100** over the opening **116** in the upper surface **112**. The tension at the fixation points in the textile-based implant **400** is minimum. Markers **122** are attached to the second end **120**c of the rods **120** such that the markers **122** are disposed about or above the plane "P" defined by the upper surface **112**. Each marker **122** is under the form of a white circle of diameter 5 mm within a black circle of diameter of 10 mm and is localized 8 mm above the textile-based implant **400**. Markers **122** provide a visual indication of the position of the rods **120**. Markers **122** are distributed on half of the textile-based implant **400** from two warp extremities.

The load simulation device **200** is positioned above the upper surface **112** of the base **110** and is configured to simulate a change in environmental loading conditions surrounding the tissue model **100** such that changes in load are generated about the tissue model **100**. The load may be referred to herein as the "intra abdominal pressure equivalent." As shown, the load simulation device **200** is a plunger **210** including a contacting surface **212** that is hemispherical (diameter 100 mm) and that is centered over the opening **116** defined through the upper surface **112**. The plunger **210** is configured to move in a direction perpendicular to the plane "P" of the upper surface **112** and exert a predetermined force, referred to hereinafter as the plunger force, against the textile-based implant **400** so that the implant **400** engages the opening **116** defined within the upper surface **112** of the tissue model **100**. The load simulation device **200** is capable of applying a quasi-static pressure (low plunger **210** descent velocity) on the textile-based implant **400** to simulate various physiological conditions. For example, the plunger force applied may be of 147 N, namely 116 mmHg, which corresponds to the intra abdominal pressure when the patient is in a standing valsalva condition. Alternatively, the plunger force applied may be of 304 N, namely 240 mmHg, which corresponds to the intra abdominal pressure when the patient jumps.

The analysis system **300** includes a digital image acquisition and processing component **310** including two cameras **312** for recording the position of the markers **122** in a 3D coordinate system and digital image correlation software **314**, namely Vic 3D™ from the company Correlated Solutions for calculating the displacement vector of each of the markers **122** resulting from bending of the rods **120** in response to the loads exerted on the textile-based implant **400** by the load simulation device **200**. The analysis system **300** records the plunger displacement **210**. The analysis system **300** also includes a mathematical software component **320** that is utilized to calculate the shear force vector at each fixation point where a marker **122** exists using the displacement vector component in the plane "P" of the markers **122** and the continuum mechanics theory applied to

7

the rods **120**. Accordingly, each shear force vector is a function of the "intra abdominal pressure equivalent." The mathematical software component **320** may include any numerical software package, such as, for example, MAT-LAB® from the company Matchworks.

An indication on the bulging of the textile-based implant **400** through the opening **116** may be given by the assessment of the plunger penetration through the opening **116**.

In an exemplary method of use, a textile-based implant **400**, such as a prosthetic knit, is placed on the upper surface **112** of the base **110** of the tissue model **100** such that the implant **400** lies along the plane "P" defined by the upper surface **112**. The implant **400** is centered placed about the opening **116** in the upper surface **112** and, as should be understood by a person of ordinary skill in the art, the orientation of the fibers of the implant **400** is controlled with respect to the upper surface **112**. The textile-based implant **400** is then directly fixed to the plurality of fixation rods **120**. A plurality of markers **122** are then affixed to a portion of the fixation rods **120** such that the markers **122** extend between the two warp extremities of the implant **400**.

With the implant **400** fixed to the tissue model **100**, the analysis system **300** is activated such that the cameras **312** capture the position of the markers **122** in a 3D coordinate system. The acquisition of the position/positional changes of the markers **122** via the cameras **312** is synchronized with the activation of the load simulation device **200** as the forces applied to the implant **400** by the load simulation device **200** is transferred to the rods **120** at the fixation points and results in bending of the rods **120**. Accordingly, any movement of the rods **120** results in movement of the markers **122** which is recorded by the cameras **312** and used in determining the shear force vector at each fixation point as described above.

As will appear from the Example below, the system of FIGS. **3** and **4** allows evaluating the properties of prosthetic knits regarding the distribution of shear forces at fixation points, bulging phenomenon and fracture at fixation points.

The advantages of the knit of the invention will appear more clearly in the Example below.

Example

Two lightweight knits of the prior art (Knits A and B) and a knit of the invention (knit C) have been produced as described below.

Knit A:
knit A is a knit of the prior art as described in WO2011/042811, namely obtained by knitting a monofilament of polyethylene terephthalate of diameter 0.08 mm on a warp knitting machine having two guide bars B1, B2, according to the following pattern, according to the ISO 11676 standard:
Bar B1: 1.0/1.2/1.0/2.3/2.1/2.3/4.5/4.3/4.5/3.2/3.4/3.2//
Bar B2: 4.5/4.3/4.5/3.2/3.4/3.2/1.0/1.2/1.0/2.3/2.1/2.3//
Guide bars B1 and B2 are threaded **1** full 1 empty and move symmetrically.

Knit B:
knit B is a knit of the prior art as described in U.S. Pat. No. 6,408,656, namely obtained by knitting a monofilament of polypropylene of diameter 0.10 mm on a warp knitting machine having two guide bars B1, B2, according to the following pattern, according to the ISO 11676 standard:
Bar B1: 5.4/4.3/2.1/0.1/1.2/3.4//
Bar B2: 0.1/1.2/3.4/5.4/4.3/2.1//
Guide bars B1 and B2 are threaded **1** full 1 empty and move symmetrically.

8

Knit C:
is a knit of the invention obtained with the knitting pattern of FIG. **1**, by knitting a monofilament of polypropylene of diameter 0.12 mm knitted on a warp knitting machine having two guide bars B1, B2, the pattern followed being the following, according to the ISO 11676 standard:
Bar B1: 1.2/4.5/4.3/4.5/4.3/1.0/1.2/1.0//
Bar B2: 4.3/1.0/1.2/1.0/1.2/4.5/4.3/4.5//
Guide bars B1 and B2 are threaded **1** full 1 empty and move symmetrically.

The following properties of knits A, Band C have been determined as follows:
Mass per unit area (g/m^2): measured according to ISO 3801:1977 «Determination of mass per unit length and mass per unit area», 5 specimens 1 dm^2.
pore size (width×height) (mm): knit biggest pores are measured making one measurement on 10 individual samples with a profile projector such as a projector 300V from ORAMA,
Bursting strength (kPa): measured according to ISO 13938-2:1999 "Textiles—Bursting properties of textiles-Pneumatic method for determining the bursting strength and bursting deformation", 5 samples
Tensile strength (N/cm) is measured through a plunger test with a traction testing machine such as the Hounsfield model H5KS (Hounsfield, Redhill, England)., crosshead speed: 50 mm/min, 5 samples: the burst pressure can be determined using a circular mesh sample with a radius of R_m=56.4 mm and with a test area of 100 cm^2 clamped at the outward boarder (modified DIN 54307 superseded standard). Then, the mesh is loaded with a spherical stamp of a radius R_s=50 mm, velocity v=50 mm/min until rupture occurs. Based on the measured forces and the resulting stretch, the tensile strength (N/cm) can be calculated;
Tear strength (N) in the warp direction and in the weft direction: measured according to ISO 4674:1977 "Textiles covered with rubber or plastic—Determination of the tear strength" Method A2, 5 samples, width: 75 mm, Tear length≤145 mm, crosshead speed: 100 mm/min,
Thickness: is measured according to ISO 9073-2:1997 "Textiles—test methods for nonwovens—Part 2: Determination of thickness", 10 samples, 100×50 mm,
Tensile breaking strength and elongation at break: is measured according to ISO 13934-1:2013 "Textiles—Tensile properties of fabrics—Part 1: Determination of maximum force and elongation at maximum force using the strip method', 5 samples, width: 50 mm, Length: 200 mm between the jaws, Crosshead speed: 100 mm/min, Pre-load: 0.5 N, using a traction testing machine such as the Hounsfield model H5KS (Hounsfield, Redhill, England);
Effective porosity: pores having a diameter above 1 mm are measured with a profile projector such as a projector 300V from ORAMA, 1 sample of 100×50 mm;
Suture pull out strength in the warp direction and in the weft direction measured according to NF S94-801: 2007 "Reinforcement implants introduced by the vaginal route for the treatment of stress urinary incontinence and/or of prolapse of the pelvic organs-preclinical trials and clinical trials"—§ 5.3.3 5 specimens 50×100 mm, USP 2 suture yarn, crosshead speed: 100 mm/min, using a traction testing machine such as the Hounsfield model H5KS (Hounsfield, Redhill, England).

The results are collected in the following tables:

TABLE I

mechanical properties						
	Knit A		Knit B		KnitC	
	Warp	Weft	Warp	Weft	Warp	Weft
Tensile breaking strength (N)	175 ± 12	129 ± 2	187 ± 16	149 ± 10	237 ± 6	201 ± 6
Elongation under 50N (%)	54 ± 0	50 ± 6	43 ± 1	59 ± 1	38 ± 1	46 ± 0
Bursting strength (kPa)	280 ± 19		361 ± 38		463 ± 19	
Tear strength (N)	22 ± 1	23 ± 2	23 ± 2	22 ± 3	30 ± 1	37 ± 5
Suture pull out strength (N)	32 ± 4	36 ± 1	33 ± 1	33 ± 2	46 ± 5	42 ± 3
Tensile strength (N/cm)	24 ± 1		40 ± 1		47 ± 1	

TABLE II

mass per unit area and porosity			
	Knit A	Knit B	Knit C
Mass per unit area (g/cm^2)	45	36	46
Thickness (mm)	0.4	0.4	0.6
Pore size (mm) (width × height)	1.5 × 1.5	1.6 × 1.4	2.0 × 2.4
Efficient porosity (%)	53	35	55

With reference to Table I above, the knit of the invention (Knit C) shows improved mechanical properties in comparison with the knits of the prior art (Knits A and B). In particular, the knit of the invention shows a higher tensile breaking strength both in warp and weft directions than Knits A and B. The knit of the invention shows a higher bursting strength than Knits A and B. The knit of the invention shows a higher tear strength both in warp and weft directions than Knits A and B.

The knit of the invention (Knit C) shows an improved suture pull out strength both in warp and weft directions compared to the knits of the prior art (knits A and B). The knit of the invention shows a higher tensile strength both in warp and weft directions than Knits A and B.

With reference to Table II above, the knit of the invention further shows an improved efficient porosity compared to Knits A and B.

In addition, the system described at FIGS. 3 and 4 has been utilized to assess the following properties of knits A, B and C under various simulated physiological conditions. For proceeding to these measures, the textile-based implant 400 of FIGS. 3 and 4 is replaced by the knit sample, either Knit A, B or C, to be evaluated.

The following properties have been evaluated:

1°) The shear forces distribution profile at fixation points of the knit: for each plunger force, namely 147 N respectively 304 N, the marker displacement as described above is transformed into the shear force at each fixation point where markers exist from the initial fixation position, using the mechanical continuum theory applied to the rods implemented in the software MATLAB® from the company Matchworks. The shear force vector is recorded. The Max and min vector norm values are recorded. The average distribution of shear forces at fixation points may be obtained under the form as shown in each of FIGS. 5 and 6, with reference to the following plunger forces, respectively:

Plunger force: 147 N Plunger force: 304 N

The shear forces distribution may be schematized by the graphic profile shown in FIG. 7.

An Average force Min-Max (N) is determined: on the example of the profile above, the Average force Min-Max (N) at a plunger force of 147 N is 3.8-8 and the Average force Min-Max (N) at a plunger force of 304 N is 7.1-13.5.

For a knit, when the range of the value of the Average force Min-Max is low, the risks of failure of the knit are decreased. The knit and therefore the abdominal wall repair will be more efficient.

In addition, the more the profile of the shear forces is close to a semi-circle or a semi-ellipse, the more regularly the shear forces are distributed. The risks of tensions in a specific direction are therefore decreased. In addition, the forces being of similar values in all directions, the knit may be implanted without having to check for a specific position of the warp or weft direction of the knit. The knit, or the prosthesis made from the knit, will also be more comfortable for the patient.

2°) The bulging indication: corresponds to the distance in mm of penetration of the plunger 210 as described in FIGS. 3 and 4, from an initial position in which its contacting surface 212 is tangent to the sample knit to a final position obtained after application of the plunger force.

A too high bulging indication, like for example above 50 mm at a plunger force of 304 N or for example above 45 mm at a plunger force of 147 N, may mean that the knit/prosthesis may be two soft for ensuring its reinforcement function of the abdominal wall, and/or may generate discomfort and/or aesthetics disturbance.

3°) The rupture of knit at fixation: the number of ruptures at fixation points is recorded.

The results are collected in the following table:

The contour profile of Knits A, B, and C are shown in FIGS. 8-10, respectively.

TABLE III

assessment of shear forces				
Knit	Average number of fracture at fixation points	Plunger force (N)	Average bulging indication (mm)	Average force Min-Max (N)
Knit A	2	147	48	3.9-4.8
		304	58.7	6.5-8.6
Knit B	2	147	44.6	2.2-5.7
		304	54.5	4.5-11.2
Knit C	0	147	40.2	3.6-8
		304	48.3	7.1-13.5

As appears from the table above, the knit of the invention (Knit C) shows a regular contour profile very close to a

semi-circle. The shear forces are therefore regularly distributed. The knit of the invention may therefore be introduced at the implantation site and implanted without the surgeon having to check previously for a specific positioning of the warp or weft direction of the knit.

In addition, the number of fracture at fixation points is 0 for the knit of the invention, whereas it is 2 for the knits of the prior art (knits A and B). The knit of the invention is therefore more reliable once sutured or tacked to the surrounding biological tissues than the knits of the prior art.

Regarding the bulging indication, the knit of the invention (knit C) shows a better bulging indication at both plunger forces than the knits of the prior art. The knit of the invention will therefore ensure its reinforcement function of the abdominal wall and will be more efficient than the knits of the prior art in physiological conditions such as jumping or coughing.

The invention claimed is:

1. A prosthetic lightweight porous knit for hernia repair comprising a monofilament of a biocompatible polymer, wherein the knit comprises a mass per unit area ranging from about 40 to about 70 g/m², an efficient porosity ranging from about 30% to about 70%, and an average bulging indication of less than 50 mm at a plunger force of 304 N or less than 45 mm at a plunger force of 147 N.

2. The prosthetic lightweight porous knit of claim 1, wherein the knit comprises a pattern followed for knitting of the monofilament on a knitting machine having a first guide bar B1 and a second guide bar B2 according to ISO 11676 standard, wherein the pattern of the first guide bar B1 is 1.2/4.5/4.3/4.5/4.3/1.0/1.2/1.0// and the pattern of the second guide bar B2 is 4.3/1.0/1.2/1.0/1.2/4.5/4.3/4.5//.

3. The prosthetic lightweight porous knit of claim 1, wherein the biocompatible polymer is selected from a group consisting of polypropylene, polyethylene terephthalate, polyamide, silicone, polyether ether ketone (PEEK), polyarylether ether ketone (PAEK), polylactic acid (PLA), polycaprolactone (PCL), polydioxanone (PDO), trimethylene carbonate (TMC), polyvinyl alcohol (PVA), polyhydroxyalkanoate (PHA), polyglycolic acid (PGA), copolymers of these biocompatible polymer materials, and mixtures thereof.

4. The prosthetic lightweight porous knit of claim 1, wherein the biocompatible polymer is polypropylene.

5. The prosthetic lightweight porous knit of claim 1, wherein a diameter of the monofilament is from about 0.10 mm to about 0.15 mm.

6. The prosthetic lightweight porous knit of claim 1, wherein a diameter of the monofilament is about 0.12 mm.

7. The prosthetic lightweight porous knit of claim 1, wherein the knit comprises a plurality of pores, each pore having a diameter above 2 mm.

8. The prosthetic lightweight porous knit of claim 1, wherein the efficient porosity of the knit is about 55%.

9. The prosthetic lightweight porous knit of claim 1, wherein the mass per unit area of the knit ranges from about 44 g/m² to about 48 g/m².

10. The prosthetic lightweight porous knit of claim 1, wherein the knit comprises a plurality of pores, each pore having a substantially hexagonal or circular shape.

11. A prosthetic lightweight porous knit for hernia repair comprising a monofilament of a biocompatible polymer, wherein the knit comprises a mass per unit area ranging from about 40 to about 70 g/m², a plurality of pores having a diameter above 2 mm, and an average bulging indication of less than 50 mm at a plunger force of 304 N or less than 45 mm at a plunger force of 147 N.

12. The prosthetic lightweight porous knit of claim 11, wherein the knit comprises a pattern followed for knitting of the monofilament on a knitting machine having a first guide bar B1 and a second guide bar B2 according to ISO 11676 standard, wherein the pattern of the first guide bar B1 is 1.2/4.5/4.3/4.5/4.3/1.0/1.2/1.0// and the pattern of the second guide bar B2 is 4.3/1.0/1.2/1.0/1.2/4.5/4.3/4.5//.

13. The prosthetic lightweight porous knit of claim 11, wherein the biocompatible polymer is selected from a group consisting of polypropylene, polyethylene terephthalate, polyamide, silicone, polyether ether ketone (PEEK), polyarylether ether ketone (PAEK), polylactic acid (PLA), polycaprolactone (PCL), polydioxanone (PDO), trimethylene carbonate (TMC), polyvinyl alcohol (PVA), polyhydroxyalkanoate (PHA), polyglycolic acid (PGA), copolymers of these biocompatible polymer materials, and mixtures thereof.

14. The prosthetic lightweight porous knit of claim 11, wherein the biocompatible polymer is polypropylene.

15. The prosthetic lightweight porous knit of claim 11, wherein a diameter of the monofilament is from about 0.10 mm to about 0.15 mm.

16. The prosthetic lightweight porous knit of claim 11, wherein a diameter of the monofilament is about 0.12 mm.

17. The prosthetic lightweight porous knit of claim 11, wherein the knit comprises an efficient porosity of about 55%.

18. The prosthetic lightweight porous knit of claim 11, wherein the mass per unit area of the knit ranges from about 44 g/m² to about 48 g/m².

19. The prosthetic lightweight porous knit of claim 11, wherein each pore of the plurality of pores has a substantially hexagonal or circular shape.

* * * * *