

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12396323
Kind Code	B2
Date of Patent	August 19, 2025
Inventor(s)	Lee; Jeong Seok et al.

Display device having protruded structure in bending region and method of providing the same

Abstract

A display device includes a substrate including a display area and a bending region which is adjacent to the display area, a pixel partition wall layer on the substrate, in the display area, and including a pixel-defining layer and a spacer which is on the pixel-defining layer, a first bending protective layer on the substrate, in the bending region, and including a base and a protrusion pattern which is on the base, and a bending inorganic layer on the first bending protective layer. The bending inorganic layer on the protrusion pattern includes an outer surface in an inverted taper shape.

Inventors: Lee; Jeong Seok (Yongin-si, KR), Kwon; Oh June (Hwaseong-si, KR), Sung; Woo Yong (Seoul, KR)

Applicant: Samsung Display Co., LTD. (Yongin-si, KR)

Family ID: 1000008764577

Assignee: SAMSUNG DISPLAY CO., LTD. (Gyeonggi-Do, KR)

Appl. No.: 17/841778

Filed: June 16, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230092412 A1	Mar. 23, 2023

Foreign Application Priority Data

KR	10-2021-0125814	Sep. 23, 2021
----	-----------------	---------------

Publication Classification

Int. Cl.: H10K50/84 (20230101); H10K50/844 (20230101); H10K71/00 (20230101); H10K77/10 (20230101); H10K102/00 (20230101)

U.S. Cl.:

CPC H10K50/844 (20230201); H10K71/00 (20230201); H10K77/111 (20230201); H10K2102/311 (20230201)

Field of Classification Search

CPC: H10K (50/844); H10K (71/00); H10K (77/111)

USPC: 257/100

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
10135028	12/2017	Kim et al.	N/A	N/A
11417860	12/2021	Lee et al.	N/A	N/A
12178071	12/2023	Lee et al.	N/A	N/A
2016/0204366	12/2015	Zhang et al.	N/A	N/A
2017/0346041	12/2016	Kim et al.	N/A	N/A
2020/0144540	12/2019	Lee et al.	N/A	N/A
2020/0243781	12/2019	Kim	N/A	H10K 77/111
2021/0066419	12/2020	Byun	N/A	H10K 59/8731
2021/0202902	12/2020	Shim	N/A	H10K 59/873
2021/0264820	12/2020	Wang et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
105679791	12/2015	CN	H01L 27/32
110112306	12/2018	CN	N/A
112164713	12/2020	CN	N/A
2020190728	12/2019	JP	G02F 1/133305
20170133812	12/2016	KR	N/A
1020180060710	12/2017	KR	N/A
20200051150	12/2019	KR	N/A
1020200059814	12/2019	KR	N/A
1020200063590	12/2019	KR	N/A
102158771	12/2019	KR	N/A

OTHER PUBLICATIONS

Primary Examiner: Dang; Phuc T

Attorney, Agent or Firm: CANTOR COLBURN LLP

Background/Summary

(1) This application claims priority to Korean Patent Application No. 10-2021-0125814 filed on Sep. 23, 2021, and all the benefits accruing therefrom under 35 U.S.C. § 119, the disclosure of which is incorporated herein by reference in its entirety.

BACKGROUND

1. Field

(2) The disclosure relates to a display device and a method of fabricating (or providing) the same. More particularly, the disclosure relates to a display device including a bending structure and a method of fabricating (or providing) the same.

2. Description of the Related Art

(3) Display devices become more important as multimedia technology evolves. As display devices, a variety of types of display devices such as liquid-crystal display (LCD) devices and organic light-emitting display (OLED) devices are used. Among them, an organic light-emitting display device is able to self-emit light and has a wide viewing angle. Accordingly, an organic light-emitting display device is attracting attention as the next generation display device.

(4) A display device includes a display area and a non-display area. The non-display area may form the bezel of the display device. Techniques for bending the display panel of a display device toward the rear side have been developed in order to reduce the bezel.

SUMMARY

(5) Although a bendable display panel has the advantage that a bezel can be reduced, layers within the display panel may be delaminated due to bending stress.

(6) Aspects of the disclosure provide a display device that can suppress delamination of a bending protective layer in a panel bending region of a display panel.

(7) It should be noted that objects of the disclosure are not limited to the above-mentioned object, and other objects of the disclosure will be apparent to those skilled in the art from the following descriptions.

(8) According to an embodiment of the disclosure, a display device includes a substrate including a display area and a bending region which is adjacent to the display area, a pixel partition wall layer on the substrate, in the display area, and including a pixel-defining layer and a spacer which is on the pixel-defining layer, a first bending protective layer on the substrate, in the bending region, and including a base and a protrusion pattern which is on the base, and a bending inorganic layer on the first bending protective layer. The bending inorganic layer on the protrusion pattern includes an outer surface in an inverted taper shape.

(9) In an embodiment, the base and the protrusion pattern may be integral with each other.

(10) In an embodiment, the pixel-defining layer and the spacer may be integral with each other, and the pixel partition wall layer and the first bending protective layer may include a same material.

(11) In an embodiment, a height of the protrusion pattern may be equal to a height of the spacer.

(12) In an embodiment, the display device may further include a second bending protective layer on the first bending protective layer.

- (13) In an embodiment, the bending inorganic layer at an upper portion of the protrusion pattern, may protrude further from the protrusion pattern (e.g., outward), than the bending inorganic layer at a lower portion of the protrusion pattern.
- (14) In an embodiment, the display device may further include an opening located where the protrusion pattern is not disposed on the base, the opening has a shadow area between the bending inorganic layer at an upper portion of the protrusion pattern and the base overlapping the bending inorganic layer.
- (15) In an embodiment, the shadow area may be filled with the second bending protective layer.
- (16) In an embodiment, the display device may further include a thin-film encapsulation layer, the encapsulation layer may be on the pixel-defining layer in the display area and include a first inorganic layer, an organic layer on the first inorganic layer, and a second inorganic layer on the organic layer.
- (17) In an embodiment, the bending inorganic layer may include a same material as at least one of the first inorganic layer and the second inorganic layer.
- (18) In an embodiment, the protrusion pattern may include a plurality of protrusions each including an outer surface in the inverted taper shape, and the protrusions may be spaced apart from one another.
- (19) According to an embodiment of the disclosure, a display device includes a substrate including a display area and a bending region which is adjacent to the display area, a plurality of pixels in the display area, a polarization layer in the display area and covering the plurality of pixels, an anti-delamination protrusion structure in the bending region and having an outer surface in an inverted taper shape, and a bending protective layer on the anti-delamination protrusion structure and in contact with an upper surface and side surfaces of the anti-delamination protrusion structure. The bending protective layer is in partial contact with the polarizing layer.
- (20) In an embodiment, the anti-delamination protrusion structure may include an organic protrusion and a bending inorganic layer which is on the organic protrusion.
- (21) In an embodiment, side surfaces of the organic protrusion may have a vertical or normal taper inclination with respect to the substrate, and side surfaces of the bending inorganic layer on the side surfaces of the organic protrusion may have an inverted taper inclination to define the inverted taper shape.
- (22) According to an embodiment of the present disclosure, a method of fabricating (or providing) a display device includes providing a substrate including a display area and a bending region which is in the display area, forming (or providing) a first bending protective layer including a base in the bending region of the substrate and a protrusion pattern which is on the base, and forming a bending inorganic layer on the first bending protective layer so that an outer surface thereof has an inverted taper shape.
- (23) In an embodiment, the forming of the bending inorganic layer may be carried out by chemical vapor deposition.
- (24) In an embodiment, the protrusion pattern may include a plurality of protrusions, and a side surface of each of the plurality of protrusions may have a vertical or normal taper inclination with respect to the substrate.
- (25) In an embodiment, the method may further include forming a second bending protective layer on the bending inorganic layer.
- (26) In an embodiment, the method may further include forming a pixel partition wall layer in the display area of the substrate, the pixel partition wall including a pixel-defining layer and a spacer which is on the pixel-defining layer, the forming of the pixel partition wall and the forming of the first bending protective layer being simultaneous.
- (27) In an embodiment, a height of the protrusion pattern may be equal to a height of the spacer.
- (28) According to an embodiment of the disclosure, it is possible to suppress the delamination of a bending protective layer by an anti-delamination structure in a panel bending region, and to

increase adhesion between the bending protective layer and the anti-delamination structure. In this manner, it is possible to reduce the radius of curvature of the bending protective layer fixing area and the panel bending region, and further reduce the dead space on the lower side of the panel. (29) It should be noted that effects of the disclosure are not limited to those described above and other effects of the disclosure will be apparent to those skilled in the art from the following descriptions.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) The above and other aspects and features of the disclosure will become more apparent by describing in detail embodiments thereof with reference to the attached drawings, in which:
- (2) FIG. 1 is a plan view of a display device according to an embodiment of the disclosure.
- (3) FIG. 2 is a cross-sectional view of a display device according to an embodiment of the disclosure.
- (4) FIG. 3 is a cross-sectional view showing a cross section of a pixel of a display area and a cross section of a non-display area of a display device according to an embodiment of the disclosure.
- (5) FIGS. 4 to 6 show cross-sectional views of a display area and a non-display area of a display device according to embodiments of the disclosure.
- (6) FIG. 7 is an enlarged view of portion A of FIG. 4.
- (7) FIG. 8 is a view for illustrating a stress applied to a panel bending region in the display panel which is bent.
- (8) FIGS. 9A and 9B are views for illustrating the principle that delamination of a second bending protective layer is prevented when a display device is bent according to an embodiment.
- (9) FIG. 10 is a cross-sectional view schematically showing a panel bending region of a display device according to an embodiment.
- (10) FIG. 11 is a perspective view showing an example of the anti-delamination structures included in the display device of FIG. 3.
- (11) FIG. 12 is a plan view showing an example of the anti-delamination structures included in the display device of FIG. 3.
- (12) FIGS. 13 to 15 are perspective views of anti-delamination structures according to embodiments of the disclosure.
- (13) FIGS. 16 and 17 are plan views of anti-delamination structures according to embodiments of the disclosure.
- (14) FIG. 18 is a perspective view of anti-delamination structures according to an embodiment of the disclosure.
- (15) FIG. 19 is a plan view of the anti-delamination structures of FIG. 18.
- (16) FIG. 20 is a perspective view of anti-delamination structures according to an embodiment of the disclosure.
- (17) FIG. 21 is a cross-sectional view of anti-delamination structures according to an embodiment of the disclosure.
- (18) FIGS. 22 to 25 are cross-sectional views for illustrating structures and processes in a method of fabricating (or providing) a display device according to an embodiment of the disclosure.
- (19) FIGS. 26A to 26C are cross-sectional views illustrating a process of depositing a bending inorganic layer by chemical vapor deposition according to an embodiment.
- (20) FIG. 27 is a view showing a force acting in a process of depositing a bending inorganic layer according to an embodiment.

DETAILED DESCRIPTION

- (21) The invention will now be described more fully hereinafter with reference to the

accompanying drawings, in which embodiments of the invention are shown. This invention may, however, be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in the art.

(22) It will also be understood that when a layer is referred to as being related to another element such as being “on” another layer or substrate, it can be directly on the other layer or substrate, or intervening layers may also be present. In contrast, when a layer is referred to as being related to another element such as being “directly on” another layer or substrate, no other layer or substrate, or intervening layer is present.

(23) The same reference numbers indicate the same or similar components throughout the specification. As used herein, a reference number may indicate a singular element or a plurality of the element. For example, a reference number labeling a singular form of an element within the drawing figures may be used to reference a plurality of the singular element within the text of specification.

(24) It will be understood that, although the terms “first,” “second,” etc. may be used herein to describe various elements, these elements should not be limited by these terms. These terms are only used to distinguish one element from another element. For instance, a first element discussed below could be termed a second element without departing from the teachings of the invention. Similarly, the second element could also be termed the first element.

(25) The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. As used herein, “a,” “an,” “the,” and “at least one” do not denote a limitation of quantity, and are intended to include both the singular and plural, unless the context clearly indicates otherwise. For example, “an element” has the same meaning as “at least one element,” unless the context clearly indicates otherwise. “At least one” is not to be construed as limiting “a” or “an.” “Or” means “and/or.” As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. It will be further understood that the terms “comprises” and/or “comprising,” or “includes” and/or “including” when used in this specification, specify the presence of stated features, regions, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, regions, integers, steps, operations, elements, components, and/or groups thereof.

(26) Furthermore, relative terms, such as “lower” or “bottom” and “upper” or “top,” may be used herein to describe one element's relationship to another element as illustrated in the Figures. It will be understood that relative terms are intended to encompass different orientations of the device in addition to the orientation depicted in the Figures. For example, if the device in one of the figures is turned over, elements described as being on the “lower” side of other elements would then be oriented on “upper” sides of the other elements. The term “lower,” can therefore, encompass both an orientation of “lower” and “upper,” depending on the particular orientation of the figure. Similarly, if the device in one of the figures is turned over, elements described as “below” or “beneath” other elements would then be oriented “above” the other elements. The terms “below” or “beneath” can, therefore, encompass both an orientation of above and below.

(27) “About” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, “about” can mean within one or more standard deviations, or within $\pm 30\%$, 20% , 10% or 5% of the stated value.

(28) Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this disclosure belongs. It will be further understood that terms, such as those defined in commonly

used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the present disclosure, and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

(29) Embodiments are described herein with reference to cross section illustrations that are schematic illustrations of idealized embodiments. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments described herein should not be construed as limited to the particular shapes of regions as illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as flat may, typically, have rough and/or nonlinear features. Moreover, sharp angles that are illustrated may be rounded. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to illustrate the precise shape of a region and are not intended to limit the scope of the present claims.

(30) Hereinafter, embodiments of the disclosure will be described in detail with reference to the accompanying drawings.

(31) FIG. 1 is a plan view of a display device **1** according to an embodiment of the disclosure. FIG. 2 is a cross-sectional view of a display device **1** according to an embodiment of the disclosure.

(32) In the plan view of FIG. 1, up-and-down directions, and right-and-left directions are defined for convenience of illustration. The up-and-down directions refer to vertical or column directions and are defined as first directions DR1. The left-and-right directions refer to horizontal or row directions and are defined as second directions DR2. A vertical direction is defined as a third direction DR3. As used herein, “upper edge,” “lower edge,” “left edge” and “right edge” of an anti-delamination structure and the like refer to edges or ends located on the upper side, the lower side, the left side and the right side of the anti-delamination structure and the like, respectively. It should be understood that the directions referred with respect to the embodiments are relative directions, and the embodiments are not limited to the directions mentioned above.

(33) Referring to FIGS. 1 and 2, a display device **1** is for displaying moving images or still images. The display device **1** may be used as the display screen of portable electronic devices such as a mobile phone, a smart phone, a tablet PC, a smart watch, a watch phone, a mobile communications terminal, an electronic notebook, an electronic book, a portable multimedia player (PMP), a navigation device and an ultra-mobile PC (UMPC), as well as the display screen of various products such as a television, a notebook, a monitor, a billboard and the Internet of Things. Examples of the display device **1** may be an organic light-emitting display device, a liquid-crystal display device, a plasma display device, a field emission display device, an electrophoretic display device, an electrowetting display device, a quantum dot light-emitting display device, a micro LED display device and the like. In the following description, an organic light-emitting display device will be described as an example of display devices. It is, however, to be understood that embodiments of the disclosure are not limited thereto.

(34) The display device **1** may include a display panel **10**. The display panel **10** may include a flexible substrate including a flexible polymer material such as polyimide. Accordingly, the display panel **10** is curvable, bendable, foldable or rollable and may be curved, bent, folded or rolled.

(35) The display panel **10** may include a main region MR and a bending region BR (otherwise referred to as a panel bending region BR) which is connected to and extended from one side of the main region MR. The display panel **10** may further include a subsidiary region SR connected to and extended from the panel bending region BR. The display panel **10** (or the display device **1**) which is bent may dispose the subsidiary region SR overlapped with the main region MR in the thickness direction (e.g., along the third direction DR3).

(36) An area (e.g., planar area) of the display panel **10** in which images are displayed is defined as a display area DPA. An area of the display panel **10** in which no image is displayed is defined as a non-display area NDA. The display area DPA of the display panel **10** is disposed in the main region

MR. A portion of the non-display area NDA is also in the main region MR. The area of the display panel **10** other than the display area DPA (e.g., remaining area) serves as the non-display area NDA of the display panel **10**. In an embodiment, the edge portion of the main region MR around the display area DPA, the entire panel bending region BR and the entire subsidiary region SR may be a non-display area NDA. It is, however, to be understood that the disclosure is not limited thereto. In an embodiment, the panel bending region BR and/or the subsidiary region SR may also include the display area DPA. Various layers or components of the display device **1** and/or the display panel **10** may include a display area DPA and a non-display area NDA corresponding to those described herein.

(37) The main region MR may have a shape generally similar to the appearance of the display device **1** when viewed from the top. The main region MR may be a flat region located in one plane. Referring to FIGS. **1** and **2**, the plane may be defined by the first direction DR1 and the second direction DR2 crossing each other. It is, however, to be understood that the disclosure is not limited thereto. At least one of the edges (e.g., edge portions) of the main region MR except for the edge (side) connected to the panel bending region BR may be bent to form a curved surface or may be bent at a right angle.

(38) The display area DPA of the display panel **10** may be disposed at the center of the main region MR or spaced apart from outer edges of the display panel **10**. The display area DPA may include pixels. Each of the pixels may include an emissive layer and a circuit layer for controlling the amount of light emitted from the emissive layer. The circuit layer may include a display line, a display electrode, and at least one transistor. The emissive layer may include an organic light-emitting material. The emissive layer may be encapsulated by an encapsulation layer. The configuration of each of the pixels will be described in detail later.

(39) The display area DPA may have a rectangular shape or a rectangular shape with rounded corners. It is, however, to be understood that the disclosure is not limited thereto. The display area DPA may have various shapes such as a square or other polygonal or circular shape, elliptical shape, etc.

(40) When at least one of the edges of the main region MR except for the edge (side) connected to the panel bending region BR is bent to form a curved surface or is bent at a right angle, the display area DPA may also be disposed at the edge. It is, however, to be understood that the disclosure is not limited thereto. The non-display area NDA that does not display image may be disposed on the curved or bent edge, or the display area DPA and the non-display area NDA may be disposed together at such inclined edge portion.

(41) In the main region MR, the non-display area NDA may be adjacent to the display area DPA, such as being located around the display area DPA. In the main region MR, the non-display area NDA may be extended from the outer boundary of the display area DPA to the edge (e.g., outer edge) of the display panel **10**. In the non-display area NDA of the main region MR, signal lines **133** and **134** (see FIG. **3**) for applying signals to the display area DPA or driving circuits may be disposed.

(42) The panel bending region BR is connected to the main region MR. In an embodiment, for example, the panel bending region BR may be connected to one end of the main region MR. A width within the display panel **10** may be taken along the second direction DR2. The width of the panel bending region BR may be less than the width (width of a shorter side) of the main region MR. The portions where the main region MR meets the panel bending region BR may be an L-shape owing to the different widths of the regions.

(43) The display panel **10** (or the display device **1**) may include a display surface as a surface furthest in the third direction DR3, without being limited thereto. At the panel bending region BR, the display panel **10** may be bent downward in the thickness direction, e.g., in the direction away from the display surface, with a curvature. Although the panel bending region BR may have a constant radius of curvature, the disclosure is not limited thereto. In an embodiment, the panel

bending region BR may define a different radii of curvature for difference sections.

(44) The display panel **10** which is flat or unbent includes a surface which is in a single plane and facing one direction. In the display panel **10** which is bent at the panel bending region BR, a facing direction of a portion of the surface of the display panel **10** is reversed. Specifically, a portion of the surface of the display panel **10** which faces upward may be bent such that the portion faces outward at the panel bending region BR (e.g., in a direction away from the display area DPA) and faces downward. As the display panel **10** is bent at the panel bending region BR, the size (e.g., planar area) of the bezel and the radius of curvature R of the display panel **10** can be reduced, and thus the dead space can be reduced within the display apparatus.

(45) However, a force to delaminate a second bending protective layer BPL (see FIG. 3) or the like may be generated due to a bending stress in the panel bending region BR by bending of the display panel **10**. As will be described later, in the display device **1** according to the embodiment, at least one anti-delamination structure D in an inverted taper shape (see FIG. 3) is formed (or provided) in the non-display area NDA including the panel bending region BR, so that it is possible to prevent the delamination of the second bending protective layer BPL. The anti-delamination structure D will be described in detail later.

(46) The subsidiary region SR is extended from the panel bending region BR. The subsidiary region SR may be extended in a direction parallel to the main region MR from the end of the bending region BR. The display device **1** which is bent may dispose the subsidiary region SR overlapping the main region MR, in the thickness direction of the display panel **10**. The display device **1** (or the display panel **10**) which is bent may dispose the subsidiary region SR overlapping the non-display area NDA at the edge of the main region MR, and overlapping the display area DPA of the main region MR.

(47) The width of the subsidiary region SR may be, but is not limited to being, equal to the width of the panel bending region BR.

(48) A driver chip **20** may be disposed on the subsidiary region SR of the display panel **10**. The driver chip **20** may include an integrated circuit for driving the display panel **10**. In an embodiment, the integrated circuit may be, but is not limited to, a data driving integrated circuit that generates and provides data signals. The driver chip **20** may be mounted on the display panel **10**, in the subsidiary region SR. The driver chip **20** may be mounted on the surface of the display panel **10** which extends from the subsidiary region SR to provide the display surface. As the panel bending region BR is bent and a portion of the surface is reversed as described above, the driver chip **20** is mounted on the portion of the surface of the display panel **10** facing downward in the thickness direction, such that the upper surface of the driver chip **20** may face downward.

(49) The driver chip **20** may be attached on the display panel **10** by an anisotropic conductive film or on the display panel **10** by ultrasonic bonding. The width of the driver chip **20** may be less than the width of the display panel **10** in the horizontal direction. The driver chip **20** is disposed at the center of the subsidiary region SR in the horizontal direction, and the left and right edges of the driver chip **20** may be spaced apart from the left and right edges of the subsidiary region SR, respectively.

(50) A pad unit (not shown) of the display panel **10** may be provided at the end of the subsidiary region SR, and a display driving substrate **30** may be connected to the pad unit. The display driving substrate **30** may be a flexible printed circuit board or film.

(51) A plurality of signal lines **133** and **134** (see FIG. 3) may be disposed in the subsidiary region SR, the panel bending region BR and the main region MR. The plurality of signal lines may be extended from the subsidiary region SR to the main region MR, via the panel bending region BR.

(52) FIG. 3 is a cross-sectional view showing a cross section of one pixel as well as a cross section of a non-display area NDA of a display device **1** according to an embodiment of the disclosure. In the cross-sectional view of FIG. 3, the display device **1** is not bent (e.g., flat or unbent) and accordingly the non-display area NDA and the display area DPA are in a same plane.

- (53) A cross-sectional structure of a pixel and a non-display area NDA of the display device **1** will be described with reference to FIG. 3.
- (54) In FIG. 3, the cross-sectional structure of the pixel is depicted on the left side, and a peripheral portion of the panel bending region BR of the non-display area NDA which is closest to the display area DPA, is depicted on the right side. As shown in FIG. 3, contact regions CT1 and CT2 may be located adjacent to the panel bending region BR. Specifically, a first contact region CT1 may be formed at the subsidiary region SR adjacent to the panel bending region BR or at the boundary thereof. A second contact region CT2 may be formed in a portion of the main region MR adjacent to the panel bending region BR or at the boundary thereof (e.g., closest to the panel bending region BR).
- (55) The layered structure of an organic light-emitting display device may include the substrate **100**, a buffer layer **105**, a semiconductor layer **110**, a first insulating layer **121**, a first conductive layer **130**, a second insulating layer **122**, a second conductive layer **140**, a third insulating layer **123**, a bending insulating layer **127**, a third conductive layer **150**, a fourth insulating layer **124**, a fourth conductive layer **160**, a fifth insulating layer **125**, a fifth conductive layer **170**, a sixth insulating layer **126**, an emissive layer **128**, a sixth conductive layer **180**, a thin-film encapsulation layer **190**, and a polarization layer POL attached by an adhesive layer **194**, as shown in FIG. 3. The first insulating layer **121**, the second insulating layer **122**, the third insulating layer **123**, the fourth insulating layer **124**, the fifth insulating layer **125**, the sixth insulating layer **126** and the bending insulating layer **127** may together define an insulating structure **120**.
- (56) Each of the layers described above may be made up of (or include) a single layer, or a stack of multiple layers. Other layers may be further disposed between the layers.
- (57) The substrate **100** supports the layers disposed thereon. The substrate **100** may be made of an insulating material such as a polymer resin. Examples of the polymer material may include polyethersulphone (PES), polyacrylate (PA), polyacrylate (PAR), polyetherimide (PEI), polyethylene naphthalate (PEN), polyethylene terephthalate (PET), polyphenylene sulfide (PPS), polyallylate, polyimide (PI), polycarbonate (PC), cellulose triacetate (CAT), cellulose acetate propionate (CAP) or a combination thereof. The substrate **100** may be a flexible substrate that can be bent, folded, or rolled. An example of the material of the flexible substrate may be, but is not limited to, polyimide (PI).
- (58) The buffer layer **105** is disposed on the substrate **100**. The buffer layer **105** may prevent impurity ions from diffusing, may prevent permeation of moisture or outside air, and may provide a flat surface. The buffer layer **105** may include silicon nitride, silicon oxide, silicon oxynitride, or the like. The buffer layer **105** covers most of the display area DPA and the non-display area NDA of the substrate **100**. However, a part of the buffer layer **105** may be removed (or excluded) from the panel bending region BR, to expose the surface of the substrate **100** to outside the buffer layer **105**. The buffer layer **105** may be eliminated depending on the type of the substrate **100**, process conditions, etc.
- (59) The semiconductor layer **110** is disposed on the buffer layer **105**. The semiconductor layer **110** forms a channel of a thin-film transistor of the pixel. The semiconductor layer **110** may include polycrystalline silicon. It is, however, to be understood that the disclosure is not limited thereto. The semiconductor layer **110** may include monocrystalline silicon, amorphous silicon, or an oxide semiconductor. The oxide semiconductor may include, for example, a binary compound (AB_x), a ternary compound (AB_xC_y) and a quaternary compound (AB_xC_yD_z) containing indium, zinc, gallium, tin, titanium, aluminum, hafnium (Hf), zirconium (Zr), magnesium (Mg), etc.
- (60) The first insulating layer **121** is disposed on the semiconductor layer **110** and may be generally disposed over the entire surface of the substrate **100**. However, the first insulating layer **121** may be removed from a part of the panel bending region BR to expose the surface of the substrate **100** to outside the first insulating layer **121**.
- (61) The first insulating layer **121** may be a gate insulating layer having a gate insulating function.

The first insulating layer **121** may include a silicon compound, a metal oxide, etc. In an embodiment, for example, the first insulating layer **121** may include silicon oxide, silicon nitride, silicon oxynitride, aluminum oxide, tantalum oxide, hafnium oxide, zirconium oxide, titanium oxide, etc. They may be used alone or in combinations. The first insulating layer **121** may be made up of a single layer or multiple layers of different materials stacked on one another.

(62) The first conductive layer **130** is disposed on the first insulating layer **121**. The first conductive layer **130** may be a first gate conductive layer. The first conductive layer **130** may include a gate electrode **131** of the thin-film transistor of the pixel and a scan line connected thereto, a storage capacitor and a first electrode **132**.

(63) The first conductive layer **130** may include at least one metal selected from the group consisting of molybdenum (Mo), aluminum (Al), platinum (Pt), palladium (Pd), silver (Ag), magnesium (Mg), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), calcium (Ca), titanium (Ti), tantalum (Ta), tungsten (W) and copper (Cu). The first conductive layer **130** may be made up of a single layer or multiple layers.

(64) A second insulating layer **122** may be disposed on the first conductive layer **130**. The second insulating layer **122** may be an interlayer dielectric layer. The second insulating layer **122** may include an inorganic insulating material such as silicon oxide, silicon nitride, silicon oxynitride, hafnium oxide, aluminum oxide, titanium oxide, tantalum oxide and zinc oxide.

(65) The second conductive layer **140** is disposed on the second insulating layer **122**. The second conductive layer **140** may be a second gate conductive layer. The second conductive layer **140** may include at least one metal selected from the group consisting of molybdenum (Mo), aluminum (Al), platinum (Pt), palladium (Pd), silver (Ag), magnesium (Mg), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), calcium (Ca), titanium (Ti), tantalum (Ta), tungsten (W) and copper (Cu). The second conductive layer **140** may be made of, but is not limited to, the same material as the first conductive layer **130**. The second conductive layer **140** may be made up of a single layer or multiple layers.

(66) The first conductive layer **130** and/or the second conductive layer **140** may include a first signal line **133** and/or a second signal line **134**, which form bending signal lines. The first signal line **133** is disposed in the subsidiary region SR located on one side of the panel bending region BR. The second signal line **134** is extended from the opposite side of the panel bending region BR, in a direction away from the subsidiary region SR, and toward the main region MR. Although the first signal line **133** disposed in the subsidiary region SR around the panel bending region BR and the second signal line **134** disposed in the main region MR are formed of a same layer (e.g., the first conductive layer **130**) in the example shown in the drawings, both of the first signal line **133** and the second signal line **134** may be formed of a same layer as the second conductive layers **140**, or one of the signal lines may be formed of the first conductive layer **130** while the other may be formed of the second conductive layer **140**. As being formed of a same layer, elements may be in a same layer as each other as respective portions of a same material layer, may be on a same layer by forming an interface with a same underlying or overlying layer, may be formed in a same process etc., without being limited thereto.

(67) A third insulating layer **123** is disposed on the second conductive layer **140**. The third insulating layer **123** may be an interlayer dielectric layer. The third insulating layer **123** may be generally disposed over the entire surface of the substrate **100**. However, the third insulating layer **123** may be removed from a part of the panel bending region BR to expose the surface of the substrate **100**.

(68) The third insulating layer **123** may include an inorganic insulating material such as silicon oxide, silicon nitride, silicon oxynitride, hafnium oxide, aluminum oxide, titanium oxide, tantalum oxide and zinc oxide, or an organic insulating material such as polyacrylates resin, epoxy resin, phenolic resin, polyamides resin, polyimides resin, unsaturated polyesters resin, polyphenylenethers resin, polyphenylenesulfides resin and benzocyclobutene (BCB). The third

insulating layer **123** may be made up of a single layer or multiple layers of different materials stacked on one another.

(69) A bending opening BOP may be defined in the panel bending region BR, and a bending insulating layer **127** may be disposed in the bending opening BOP.

(70) As described above, portions of the buffer layer **105**, the first insulating layer **121**, the second insulating layer **122** and the third insulating layer **123** may be removed or removed from the panel bending region BR, to expose the upper surface of the substrate **100** to outside these respective layers. As such, the exposed region of the substrate **100** at the panel bending region BR from which a plurality of insulating layers is removed, may be defined as the bending opening BOP. Opposing sidewalls which define the bending opening BOP may be defined by the side surfaces of the buffer layer **105**, the first insulating layer **121**, the second insulating layer **122** and the third insulating layer **123** stacked on one another. The various side surfaces of the layers defining the bending opening BOP may be aligned with one another.

(71) The bending opening BOP may be filled with the bending insulating layer **127**. The lower surface of the bending insulating layer **127** which is closest to the substrate **100** may be in direct contact with the surface of the substrate **100** which is exposed via the bending opening BOP. The sidewalls of the buffer layer **105**, the first insulating layer **121**, the second insulating layer **122** and the third insulating layer **123** forming the bending opening BOP may be exposed to outside these layers by the bending opening BOP. Although FIG. 3 shows that the upper surface of the bending insulating layer **127** which is furthest from the substrate **100**, is located at the same level as the upper surface of the third insulating layer **123** (e.g., coplanar), the disclosure is not limited thereto.

(72) The bending insulating layer **127** may be a via layer including an organic material. The bending insulating layer **127** may include an organic insulating material such as polyacrylate resin, epoxy resin, phenolic resin, polyamide resin, polyimide resin, unsaturated polyesters resin, poly phenylene ether resin, poly phenylene sulfide resin, and benzocyclobutene (BCB).

(73) The third conductive layer **150** is disposed on the third insulating layer **123**. The third conductive layer **150** may be a first source/drain conductive layer. The third conductive layer **150** may include a first electrode **151** and a second electrode **152** of the thin-film transistor of the pixel, and a first supply voltage electrode **153**. The first electrode **151** and the second electrode **152** of the thin-film transistor may be electrically connected to the source region and the drain region of the semiconductor layer **110**, respectively, through contact holes passing through the third insulating layer **123**, the second insulating layer **122** and the first insulating layer **121**.

(74) The third conductive layer **150** may include at least one metal selected from the group consisting of aluminum (Al), molybdenum (Mo), platinum (Pt), palladium (Pd), silver (Ag), magnesium (Mg), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), calcium (Ca), titanium (Ti), tantalum (Ta), tungsten (W) and copper (Cu). The third conductive layer **150** may be made up of a single layer or multiple layers. For example, the third conductive layer **150** may have a stacked structure of Ti/Al/Ti, Mo/Al/Mo, Mo/AlGe/Mo, and Ti/Cu.

(75) The fourth insulating layer **124** is disposed on the third conductive layer **150**. The fourth insulating layer **124** covers the third conductive layer **150**. The fourth insulating layer **124** may be a via layer. The fourth insulating layer **124** may include the same material as the above-described bending insulating layer **127** or may include one or more materials selected from the materials listed above as the materials of the bending insulating layer **127**.

(76) The fourth insulating layer **124** may cover the third conductive layer **150**, the third conductive layer **150** and the bending insulating layer **127**, and may be disposed on an entirety of them. That is to say, the fourth insulating layer **124** may be disposed not only in the display area DPA but also in the panel bending region BR and a periphery thereof (e.g., peripheral portion of the non-display area NDA which is closest to the display area DPA). The upper surface of the fourth insulating layer **124** may have the same level in the display area DPA and the panel bending region BR (e.g., upper surfaces coplanar with each other), but the disclosure is not limited thereto.

(77) The fourth conductive layer **160** is disposed on the fourth insulating layer **124**. The fourth conductive layer **160** may be a second source/drain conductive layer. The fourth conductive layer **160** may include a data line **161**, a connection electrode **162**, and a first supply voltage line **163** of the pixel. In the pixel, the data line **161** may be electrically connected to the first electrode **151** of the thin-film transistor of the pixel through a contact hole penetrating through the fourth insulating layer **124**. The connection electrode **162** may be electrically connected to the second electrode **152** of the thin-film transistor of the pixel through the contact hole passing through the fourth insulating layer **124**. The first supply voltage line **163** may be electrically connected to the first supply voltage electrode **153** through a contact hole passing through the fourth insulating layer **124**.

(78) The fourth conductive layer **160** may further include a connection line layer **164** traversing the panel bending region BR. The connection line layer **164** may be electrically connected to the first signal line **133** and the second signal line **134**, through at least one contact hole penetrating the fourth insulating layer **124**.

(79) The fourth conductive layer **160** may include at least one metal selected from the group consisting of aluminum (Al), molybdenum (Mo), platinum (Pt), palladium (Pd), silver (Ag), magnesium (Mg), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), calcium (Ca), titanium (Ti), tantalum (Ta), tungsten (W) and copper (Cu). The fourth conductive layer **160** may be made up of a single layer or multiple layers. The fourth conductive layer **160** may be made of, but is not limited to, the same material as the third conductive layer **150**.

(80) The fourth conductive layer **160** forming the connection line layer **164** may include aluminum, which is a material having a flexible characteristic. In an embodiment, for example, the third conductive layer **150** and the fourth conductive layer **160** may include a stack of layers of Ti/Al/Ti.

(81) Although the fourth conductive layer **160** is used as the connection line layer **164** in the embodiment, the disclosure is not limited thereto. The third conductive layer **150** may be used as the connection line layer **164**, or the third conductive layer **150** as well as the fourth conductive layer **160** may be used together as a connection layer.

(82) The fifth insulating layer **125** is disposed on the fourth conductive layer **160**. The fifth insulating layer **125** may cover all of the fourth conductive layer **160** and the connection line layer **164**, and may be disposed on the entire surface thereof. That is to say, the fifth insulating layer **125** may be disposed not only on the display area DPA but also on the panel bending region BR and its periphery. The upper surface of the fifth insulating layer **125** may have the same level in the display area DPA and the panel bending region BR in the display panel **10** which is not bent, but the disclosure is not limited thereto. The fifth insulating layer **125** may be a via layer. The fifth insulating layer **125** may include the same material as the above-described bending insulating layer **127** or may include one or more materials selected from the materials listed above as the materials of the bending insulating layer **127**.

(83) The fifth conductive layer **170** is disposed on the fifth insulating layer **125** in the display area DPA. The anode electrode of the pixel may be formed of the fifth conductive layer **170**. The anode electrode may be electrically connected to the connection electrode **162** formed of the fourth conductive layer **160**, through the contact hole formed in the fifth insulating layer **125**, and may be connected to the second electrode **152** of the thin-film transistor therethrough.

(84) The fifth conductive layer **170** may have a stacked structure of a material layer having a high work function such as indium-tin-oxide (ITO), indium-zinc-oxide (IZO), zinc oxide (ZnO) and indium oxide (In.sub.2O.sub.3), and a reflective material layer such as silver (Ag), magnesium (Mg), aluminum (Al), platinum (Pt), lead (Pd), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), lithium (Li), calcium (Ca) or a combination thereof. A layer having a higher work function may be disposed on a reflective material layer so that the higher work function layer is disposed closer to the emissive layer **128**. The fifth conductive layer **170** may have, but is not limited to, a multilayer structure of ITO/Mg, ITO/MgF, ITO/Ag, and ITO/Ag/ITO.

(85) A sixth insulating layer **126** may be disposed on the fifth conductive layer **170**. The sixth

insulating layer **126** includes a pixel partition wall layer in the display area DPA and the non-display area NDA. The pixel partition wall layer includes a pixel partition wall **126a** disposed in the display area DPA, and a first bending protective layer **126b** disposed in the non-display area NDA.

(86) The pixel partition wall **126a** located in the display area DPA may include a pixel-defining layer **126a_1** including (or defining) an opening exposing the fifth conductive layer **170** forming the anode electrode to outside the sixth insulating layer, and a plurality of spacers **126a_2** which are disposed on the pixel-defining layer **126a_1** and protruding in the third direction DR3 (e.g., in a direction away from the substrate **100**). The spacer **126a_2** may be disposed corresponding to the pixel-defining layer **126a_1** and may have a width smaller than that of the pixel-defining layer **126a_1** in a direction along the substrate **100**.

(87) The first bending protective layer **126b** located in the non-display area NDA includes a base **126b_1** and a protrusion pattern **126b_2** which is disposed on the base **126b_1** and protruding in the third direction DR3 from the **126b_1**. The base **126b_1** covers at least the entire panel bending region BR. The base **126b_1** may have a constant thickness across different regions, but the disclosure is not limited thereto.

(88) The protrusion pattern **126b_2** may include one or more protrusions PT. Each of the protrusions PT in a plurality of protrusions PT may have a rectangular cross-sectional structure. That is to say, as shown in the drawings, the side surfaces of the protrusions PT may be disposed on the plane perpendicular to the substrate **100**. It should be understood, however, that the disclosure is not limited thereto. In the cross-sectional view, the sidewalls of the protrusions PT in the third direction DR3 may include inverted taper inclined surfaces, normal taper inclined surfaces (e.g., in a direction normal to the substrate **100**) or curved inclined portions. In an embodiment, for example, an organic protrusion (e.g., the protrusion PT) includes side surfaces extended normal with respect to the substrate **100** or extended inclined with respect to the substrate **100**, and the bending inorganic layer **290** extends along the side surfaces of the organic protrusion to have an inverted taper inclination.

(89) The protrusions PT are spaced apart from one another along the base **126b_1**. The base **126b_1** may include regions where the protrusions PT are disposed and regions where the protrusions PT are not disposed. These regions may be arranged alternately. Accordingly, the first bending protective layer **126b** may have depression/elevations on the surface depending on whether the protrusions **126b_2** are disposed or not.

(90) The base **126b_1** of the first bending protective layer **126b** may have the same height (or thickness along the third direction DR3) as the pixel-defining layer **126a_1** of the pixel partition wall **126a**. The protrusion pattern **126b_2** may have the same height as the spacer **126a_2** of the pixel partition wall **126a**. It should be understood, however, that the disclosure is not limited thereto. The pixel-defining layer **126a_1** and the base **126b_1** may together form a base layer from which the spacers **126a_2** and the protrusion pattern **126b_2** protrude.

(91) According to this embodiment, the pixel-defining layer **126a_1** and the spacer **126a_2** are integrally formed of the same material, and the base **126b_1** and the protrusion pattern **126b_2** are integrally formed. It should be understood, however, that the disclosure is not limited thereto. In an embodiment, for example, the pixel-defining layer **126a_1** and the base **126b_1** may be made of a first insulating material, and the spacer **126a_2** and the protrusion pattern **126b_2** may be made of a second insulating material, such as to form a stacked structure.

(92) The sixth insulating layer **126** may include an inorganic insulating material such as silicon oxide, silicon nitride, silicon oxynitride, hafnium oxide, aluminum oxide, titanium oxide, tantalum oxide and zinc oxide, or an organic insulating material such as polyacrylates resin, epoxy resin, phenolic resin, polyamides resin, polyimides resin, unsaturated polyesters resin, polyphenylenethers resin, polyphenylenesulfides resin and benzocyclobutene (BCB). In the following description, an example is illustrated where the sixth insulating layer **126** includes an organic

insulating material.

(93) The emissive layer **128** is disposed in the opening of the pixel-defining layer **126a_1** as solid portions of the pixel partition wall **126a**. The emissive layer **128** may include an organic emissive layer made of an organic semiconductor material, etc., or an inorganic emissive layer made of an inorganic semiconductor material. When the emissive layer **128** includes an organic semiconductor material, the emissive layer **128** may include an organic emissive layer, a hole injection/transport layer, and an electron injection/transport layer.

(94) The sixth conductive layer **180** is disposed on the emissive layer **128**. The sixth conductive layer **180** may be disposed on the emissive layer **128** of the display area DPA, the pixel-defining layer **126a_1** and the spacer **126a_2**, but may not be disposed in the non-display area NDA. The cathode electrode may be implemented as the sixth conductive layer **180**. The cathode electrode CAT may be disposed over throughout the display area DPA. The sixth conductive layer **180** may include a material having a small work function such as Li, Ca, LiF/Ca, LiF/Al, Al, Mg, Ag, Pt, Pd, Ni, Au, Nd, Ir, Cr, BaF, Ba, or a compound or combination thereof. The sixth conductive layer **180** may further include a transparent metal oxide layer disposed on the material layer having a small work function.

(95) The thin-film encapsulation layer **190** including a first inorganic layer **191**, an organic layer **192** and a second inorganic layer **193** is disposed on the sixth conductive layer **180** in the display area DPA. The organic layer **192** can be encapsulated by the first inorganic layer **191** and the second inorganic layer **193**.

(96) The first inorganic layer **191** and the second inorganic layer **193** may include one or more materials selected from the group consisting of silicon nitride, aluminum nitride, zirconium nitride, titanium nitride, hafnium nitride, tantalum nitride, silicon oxide, aluminum oxide, titanium oxide, tin oxide, cerium oxide, silicon oxynitride (SiON), etc.

(97) The organic layer **192** may include an organic insulating material such as polyacrylate resin, epoxy resin, phenolic resin, polyamide resin, polyimide resin, unsaturated polyesters resin, polyphenylene ether resin, polyphenylene sulfide resin, and benzocyclobutene (BCB).

(98) A bending inorganic layer **290** may be disposed on the protrusion pattern **126b_2** in the non-display area NDA. According to an embodiment of the disclosure, the bending inorganic layer **290** may be formed via the same material and the same process as the first inorganic layer **191**. As another example, the bending inorganic layer **290** may be formed in the same layer and via the same process as the second inorganic layer **193**. As another example, the bending inorganic layer **290** may be formed as a stack of the first inorganic layer **191** and the second inorganic layer **193**. It should be understood, however, that the embodiments of the disclosure are not limited thereto. The bending inorganic layer **290** may be made of a different material and via a different process from the first inorganic layer **191** and the second inorganic layer **193**.

(99) The bending inorganic layer **290** together with the protrusions PT thereunder forms an anti-delamination structure D having an inverted taper shape in cross-section. The anti-delamination structure D will be described in detail later.

(100) A polarization layer POL is disposed on the thin-film encapsulation layer **190** and may have a polarization axis. The polarization layer POL may be attached to the thin-film encapsulation layer **190** by the adhesive layer **194** in the display area DPA. Light is emitted from the emissive layer **128**, and the polarization layer POL may transmit only light that vibrates in the same direction as the polarization axis, while absorbing or reflecting light that vibrates in other directions.

(101) The second bending protective layer BPL may be applied on the anti-delamination structure D of the non-display area NDA and may cover the non-display area NDA including the panel bending region BR.

(102) The second bending protective layer BPL may include an ultraviolet-curable (UV-curable) resin, a thermosetting resin, or an electron-beam-curable resin. The second bending protective layer BPL may include acrylic or silicone-based resin, and may further include fine particles of polymer

series such as rubber containing silica, epoxy, and an epoxy hybrid. It should be understood, however, that the disclosure is not limited thereto. The second bending protective layer BPL may be formed by attaching a layer such as polyethylene ether phthalate (PET) in a single structure or stacked structure.

(103) As used herein, a height may be taken from a reference, such as an upper surface of the substrate **100**. The height of the upper surface of the second bending protective layer BPL may be substantially equal to the height of the upper surface of the polarization layer POL, but the embodiments of the disclosure are not limited thereto. The arrangement relationships between the polarization layer POL and the second bending protective layer BPL will be described with reference to FIGS. **4** to **6**.

(104) FIGS. **4** to **6** show cross-sectional views of a display area DPA and a non-display area NDA of a display device **1** according to various embodiments of the disclosure.

(105) In order to describe in detail the relationship between the polarization layer POL disposed in the display area DPA and the second bending protective layer BPL disposed in the non-display area NDA, FIGS. **4** to **6** briefly depict a plurality of insulating layers disposed on the entirety surface of the display area DPA and the non-display area NDA, and depict an example where a support member **101** is further disposed under the substrate **100**. The support member **101** can support the substrate **100** and can impart rigidity to the substrate **100**. The support member **101** may not be disposed in the panel bending region BR so that it does not hinder bending of the substrate **100**. The support member **101** may include, for example, polyethylene terephthalate (PET).

(106) As shown in FIGS. **4** to **6**, the second bending protective layer BPL may be at least partially in contact with the polarization layer POL.

(107) In embodiments, the second bending protective layer BPL may be in contact with a side surface which is closest to the panel bending region BR (e.g., the side surface extended in the third direction DR3) of the polarization layer POL. The second bending protective layer BPL may be in contact with a lower portion of one side surface of the polarization layer POL while exposing a part of the upper portion further from the substrate **100** than the lower portion as shown in FIG. **4**, or may be in contact with an entirety of the side surface of the polarization layer POL as shown in FIG. **5**. Furthermore, as shown in FIG. **6**, the second bending protective layer BPL not only may cover the side surface of the polarization layer POL, but also may be extended from the side surface to the upper surface of the polarization layer POL, to cover a part of upper surface of the polarization layer POL which is furthest from the substrate **100**.

(108) As such, the portion where the second bending protective layer BPL meets the polarization layer POL (e.g., an interface therebetween) and the periphery of the non-display area NDA, may be located in the main region MR, and may be generally located between the panel bending region BR and the display area DPA. Accordingly, the portion where the second bending protective layer BPL meets the polarization layer POL, and the periphery, are not bent in the display device **1** which is bent, and thus the anti-delamination structure D may be excluded from such unbent portion. In the following description, the area of the second bending protective layer BPL extended from the panel bending region BR toward the display area DPA is referred to as a fixing area F of the second bending protective layer BPL.

(109) Hereinafter, the anti-delamination structure D in the inverse taper shape will be described in detail.

(110) FIG. **7** is an enlarged cross-sectional view of portion A of FIG. **4**.

(111) Referring to FIGS. **3** and **7**, the bending inorganic layer **290** together with the protrusions PT thereunder, form the anti-delamination structures D. In other words, the anti-delamination structures D include the protrusions PT and the bending inorganic layer **290** which is disposed on the protrusions PT, to provide an anti-delamination protrusion structure. The upper surface structure of the anti-delamination structures D is defined by the upper surface structure of the bending inorganic layer **290**.

(112) The bending inorganic layer **290** is disposed on the first bending protective layer **126b**. Specifically, the bending inorganic layer **290** is disposed on the upper surface of the protrusions PT, opposing side surfaces of the protrusions PT, and the upper surface of the base **126b_1**. According to this embodiment, an outer inclined surface DP1 of the bending inorganic layer **290** disposed on the protrusions PT has a straight shape, but the disclosure is not limited thereto. The outer inclined surface DP1 may include a partially curved surface.

(113) As shown in FIG. 7, the distance from the axis (indicated by line I-I') extended in the vertical direction through the anti-delamination structure D, to the outer inclined surface DP1 of the bending inorganic layer **290** disposed on the protrusion PT, becomes narrower from the upper portion to the lower portion of the anti-delamination D. That is, the distance decreases in a direction from the second bending protective layer BPL toward the first bending protective layer **126**. The outer inclined surface DP1 of the bending inorganic layer **290** disposed on the protrusion PT has an inverted taper shape. Accordingly, a first angle $\theta 1$ formed by the outer inclined surface DP1 of the bending inorganic layer **290** disposed on the protrusions PT, and an upper base surface DP3 of the bending inorganic layer **290** disposed on the upper surface of the base **126b_1** which is between protrusions PT, may be an acute angle. In addition, a second angle $\theta 2$, which is the internal angle of a protruding portion **290a** formed at a corner where an upper protrusion surface DP4 of the bending inorganic layer **290** and the outer inclined surface DP1 meet, may also be an acute angle. Since the anti-delamination structure D has a substantially vertically symmetrical shape and a width defined by a width of the bending inorganic layer **290**, the anti-delamination structure D may form an inverted taper shape in which the width of the upper portion of the anti-delamination structure D is greater than the width of the lower portion thereof, in the horizontal direction of FIG. 7.

(114) Referring to FIG. 7, adjacent anti-delamination structures D may define an opening W, as a recess, therebetween. The opening W may be located at a position where the protrusion PT is not disposed, and may be defined by the outer inclined surface DP1 of the bending inorganic layer **290** disposed on the protrusion PT, the inclined surface DP2 facing the outer inclined surface DP1, and the upper base surface DP3 of the bending inorganic layer **290** disposed on the upper surface of the base **126b_1**. The width of the opening W becomes narrower (e.g., decreases) toward the upper side of the anti-delamination structure D.

(115) According to an embodiment of the disclosure, the second bending protective layer BPL may also be disposed in the opening W formed by the anti-delamination structures D adjacent to each other. As shown in FIG. 7, the opening W includes a shadow area W_sh covered by the anti-delamination structure D at the lower portion of the anti-delamination structure D. The shadow area W_sh may be defined by an imaginary line II-II' drawn from a protruding portion **290a** at the upper portion of the anti-delamination structure D, to the base **126b_1** of the first bending protective layer **126b**, the outer inclined surface DP1 of the bending inorganic layer **290** disposed on the protrusion PT and a portion of the upper base surface DP3 of the bending inorganic layer **290** disposed on the upper surface of the base **126b_1**. The second bending protective layer BPL may be used to fill the entire opening W including the shadow area W_sh. It is possible to suppress the delamination of the part of the second bending protective layer BPL located in the shadow area W_sh by the anti-delamination structure D covering the part of the second bending protective layer BPL. The principle that the shadow area W_sh defined by the anti-delamination structure D contributes to the suppression of delamination of the second bending protective layer BPL will be described with reference to FIGS. 8 and 9.

(116) FIG. 8 is a view for illustrating a stress applied to a panel bending region BR when the display panel **10** is bent.

(117) FIG. 8 is a view for illustrating a bending stress applied to a second layer **201** when first and second layers **200** and **201** contiguous to each other are bent with a radius of curvature R. When the second layer **201** is disposed on the first layer **200**, a tensile bending stress B is applied to the

second layer **201**, while a compressive bending stress A is applied to the first layer **200**.

(118) As such, when bending stresses in different directions are applied, cracks may occur in the first layer **200** and the second layer **201**, or the first layer **200** may be delaminated from the second layer **201**. The layers **200** and **201** may be delaminated in the thickness direction perpendicular to an interface therebetween.

(119) FIGS. **9A** and **9B** are views for illustrating the principle that delamination of a second bending protective layer BPL is prevented when a display device **1** is bent according to an embodiment. FIG. **9B** is an enlarged view of portion E in FIG. **9A**.

(120) As described above with reference to FIG. **8**, when the anti-delamination structure D and the second bending protective layer BPL which is disposed on the anti-delamination structure D are bent together to have a radius of curvature R, a tensile stress B is applied to the second bending protective layer BPL while a compressive stress A is applied to the anti-delamination structure D.

(121) When the stresses in the different directions are applied as described above, a force to delaminate the second bending protective layer BPL applied on the panel bending region BR from the anti-delamination structure D may act. Such a force may generally work in the vertical direction of the opening W (e.g., along the thickness direction of the display device **1**).

(122) Referring to FIG. **9B**, a force to delaminate the second bending protective layer BPL may be applied in the opening W along the thickness direction due to the bending stress (e.g., upward arrows in FIG. **9B**). Since the second bending protective layer BPL located in the shadow area W_{sh} of the opening W may be in contact with the outer inclined surface DP1 of the anti-delamination structure D, a resistance against the force to delaminate the second bending protective layer BPL may be generated.

(123) Specifically, according to the embodiment of the disclosure, the outer surface (or the outer inclined surface DP1) of the anti-delamination structure D which extends to the protruding portion **290a**, covers the part of the second bending protective layer BPL located in the shadow area W_{sh} at a lower portion the anti-delamination structure D. Thus, the outer surface of the anti-delamination structure D which is over the part of the second bending protective layer BPL located in the shadow area W_{sh} acts as a direct resistance to the delamination. In addition, since a larger contact area is obtained by the inclined surfaces of the anti-delamination structure D with respect to the second bending protective layer BPL within the opening W, resistance against the force may be imparted by friction at the interface between these two layers. Accordingly, the anti-delamination structure D can increase the resistance against the delamination force to weaken the delamination force, and can improve the adhesion between the second bending protective layer BPL and the anti-delamination structure D which form an interface therebetween.

(124) Incidentally, the width of the opening W formed by outer surfaces of the adjacent anti-delamination structures D may become larger (e.g., may increase) by bending of the display panel **10** at the panel bending region BR, as compared to an original opening width of the opening W in the display panel **10** which is not bent at the panel bending region BR. When the anti-delamination structure D maintains the inverted taper shape, even in the display panel **10** which is bent as shown in FIGS. **9A** and **9B**, however, it is possible to more effectively suppress the delamination of the second bending protective layer BPL from other layers such as the second bending protective layer BPL.

(125) FIG. **10** is a cross-sectional view schematically showing a panel bending region BR of a display device **1** which is bent, according to an embodiment.

(126) As shown in FIG. **10**, when the panel bending region BR of the display device **1** according to an embodiment is bent, the display device **1** has the radius of curvature R. As the radius of curvature R decreases, the bending stress acting on the second bending protective layer BPL and the anti-delamination structure D increases. As described above, it is possible to prevent delamination of the second bending protective layer BPL from the anti-delamination structures D, by the anti-delamination structures D. In this manner, it is possible to improve the adhesion

between the second bending protective layer BPL and the anti-delamination structures D.

(127) As a result, the adhesion between the second bending protective layer BPL and the anti-delamination structure D can be improved to reduce the fixing area F of the second bending protective layer BPL described above, which reduces the dead space on the lower side of the display panel **10**. Additionally, the radius of curvature R can be reduced, thereby further reducing the dead space on the lower side of the display panel **10**.

(128) In addition, as the anti-delamination structures D are arranged regularly and the adhesion between the anti-delamination structures D and the second bending protective layer BPL is improved, a material of the second bending protective layer BPL can be spread more easily when the second bending protective layer BPL is provided on the anti-delamination structures D, so that it is possible to prevent defects such as bubbles.

(129) Hereinafter, a variety of layouts of the anti-delamination structures D each having the inverted taper shape will be described.

(130) FIG. **11** is a perspective view showing an example of the anti-delamination structures D included in the display device **1** of FIG. **3**. FIG. **12** is a plan view showing an example of the anti-delamination structures D included in the display device **1** of FIG. **3**.

(131) Referring to FIGS. **11** and **12**, the anti-delamination structures D according to an embodiment of the disclosure may have the cross section in the inverted taper shape, and may include a rectangular or square shape when viewed from the top (e.g., planar shape) in order to increase the resistance against the delamination direction when a delamination force is applied in the thickness direction (indicated as the third direction DR3 in the drawing for convenience of illustration). It is, however, to be understood that the disclosure is not limited thereto. In an embodiment, for example, the upper surface of the anti-delamination structures D may have a quadrangular shape in which adjacent sides form an acute angle or an obtuse angle when viewed from the top.

(132) Although all of the four sides of the anti-delamination structures D form the inverted taper shape according to the embodiment of the disclosure, the disclosure is not limited thereto. In an embodiment, for example, the anti-delamination structures D may include the inverted taper shape only on some of the opposing surfaces, while the other surfaces may not include the inverted taper shape.

(133) As shown in FIG. **12**, the plurality of anti-delamination structures D may be spaced apart from one another at a distance in the first direction DR1 and in the second direction DR2 and may be arranged in a matrix pattern when viewed from the top. According to this embodiment, the separation distances in the first direction DR1 and the second direction DR2 between the anti-delamination structures D are uniform, but the disclosure is not limited thereto.

(134) FIGS. **13** to **15** are perspective views of anti-delamination structures D according to various embodiments of the disclosure.

(135) The embodiment of FIG. **13** is different from the embodiment of FIG. **11** in that the anti-delamination structures D have a circular shape when viewed from the top. Specifically, according to this embodiment, the anti-delamination structures D have an inverted taper shape having a circular upper surface and the width (or dimension) decreasing toward the lower side (e.g., the width decreases in a direction from the upper surface to the base **126b_1** of the first bending protective layer **126b**). The plana shape of the anti-delamination structures D taken in the horizontal direction may be circular, but the disclosure is not limited thereto.

(136) According to this embodiment, the upper surface of the anti-delamination structures D may have a shape in which the upper surface protrudes further toward the adjacent anti-delamination structures D than the lower surface, so that the opening width of the opening W formed by the adjacent anti-delamination structures D becomes narrower (or decreases) in a direction toward the upper side of the anti-delamination structures D from the base **126b_1**. With such a structure, it is possible to suppress the delamination of the second bending protective layer BPL from another layer as the above-described shadow area W_sh is formed.

(137) The embodiment of FIG. 14 is different from the embodiment of FIG. 11 in that anti-delamination structures D include one or more concave surfaces as side surfaces.

(138) Specifically, according to this embodiment, the upper surface and the outer inclined surface DP1 of each of the anti-delamination structures D may include a concave surface depressed toward the center of a respective anti-delamination structure D. In a top plan view, a protruding portion 290a may be disposed at a corner where adjacent concave surfaces meet in each of the anti-delamination structures D.

(139) According to this embodiment, a contact area with the second bending protective layer BPL is increased by the concave surfaces of the anti-delamination structures D. In addition, since the outer inclined surface DP1 has the inverted taper shape, the shadow area W_sh can be formed, thereby effectively suppressing the delamination of the second bending protective layer BPL.

(140) The embodiment of FIG. 15 is different from the embodiment of FIG. 11 in that each of anti-delamination structures D has a polygonal cross-section, and includes a first inclined portion TP1 having a first slope, and a second inclined portion TP2 having a second slope under the first inclined portion TP and closer to the base 126b_1. The first slope is different from the second slope, and at least one of the slopes forms an inverted taper slope.

(141) Also in this embodiment, the shadow area W_sh can be formed under the first inclined portion TP1 and/or the second inclined portion TP2 to suppress the delamination of the second bending protective layer BPL.

(142) FIGS. 16 and 17 are plan views of anti-delamination structures D according to various embodiments of the disclosure.

(143) The embodiment of FIG. 16 is different from the embodiment of FIG. 12 in that adjacent anti-delamination structures D have different planar areas when viewed from the top.

(144) Specifically, according to this embodiment, the anti-delamination structures D include first anti-delamination structures D1 having a first area (e.g., first planar area) and second anti-delamination structures D2 having a second area (e.g., second planar area) larger than the first area when viewed from the top, which are arranged alternately in the second direction DR2.

(145) According to an embodiment of the disclosure, in the second direction DR2, the width of the first anti-delamination structures D1 may be smaller than the width of the second anti-delamination structures D2 spaced apart from an adjacent first anti-delamination structure D in the second direction DR2. In the first direction DR1, the width of the first anti-delamination structures D1 may be equal to that of the second anti-delamination structures D2 when viewed from the top. It is, however, to be understood that the disclosure is not limited thereto. In an embodiment, for example, the first anti-delamination structures D1 and the second anti-delamination structures D2 may include a circular shape or the like when viewed from the top.

(146) Although the first anti-delamination structures D1 and the second anti-delamination structures D2 are arranged in the second direction DR2 in the drawings, the anti-delamination structures D having different widths may be alternately arranged in the first direction DR1.

(147) The embodiment of FIG. 17 is different from the embodiment of FIG. 12 in that anti-delamination structures D are arranged in staggered rows in the second direction DR2 when viewed from the top.

(148) Specifically, the first anti-delamination structures D1 and the second anti-delamination structures D2 are alternately arranged in the second direction DR2, and may be staggered with each other in the second direction DR2.

(149) It is, however, to be understood that this is merely illustrative but is not limiting. In an embodiment, for example, the first anti-delamination structures D1 and the second anti-delamination structures D2 have a circular shape or the like when viewed from the top, and the area of the first anti-delamination structures D1 may be different from that of the second anti-delamination structures D2 spaced apart from them in the second direction DR2.

(150) Accordingly, when the second bending protective layer BPL applied in the opening W formed

by the first anti-delamination structures **D1** adjacent to each other in the first direction **DR1** is delaminated, it is possible to prevent that the second anti-delamination structures **D2** adjacent to each other in the second direction **DR2** are delaminated one after another.

(151) FIG. **18** is a perspective view of anti-delamination structures **D** according to an embodiment of the disclosure. FIG. **19** is a plan view of the anti-delamination structures **D** of FIG. **18**.

(152) According to the embodiments of FIGS. **18** and **19**, anti-delamination structures **D** in an inverted taper shape are arranged adjacent to each other in the first direction **DR1** such that they are spaced apart from one another at a constant distance, and may be extended in the second direction **DR2** in the form of lines (e.g., stripes) to have a major dimension in the second direction **DR2**. As shown in FIGS. **18** and **19**, an anti-delamination structure width **S1** of an anti-delamination structure **D** in the first direction **DR1** when viewed from the top may be equal to the anti-delamination structure width **S1** of another anti-delamination structure **D** spaced apart from it in the first direction **DR1** and disposed in the form of line. It should be understood, however, that the disclosure is not limited thereto. The distance between adjacent anti-delamination structures **D** spaced apart from each other in the first direction **DR1** may be different, or different anti-delamination structures **D** may have different anti-delamination structure widths **51** and/or distances.

(153) FIG. **20** is a perspective view of anti-delamination structures **D** according to an embodiment of the disclosure.

(154) The embodiment of FIG. **20** is different from the embodiment of FIG. **18** in that anti-delamination structures **D** are extended and arranged in a different direction.

(155) That is to say, the anti-delamination structures **D** may be spaced apart from one another in the second direction **DR2**, and may be extended in the first direction **DR1** in the form of lines.

(156) According to the above-described embodiments of FIGS. **18** and **20**, line-shaped shadow areas **W_sh** may be formed under the anti-delamination structures **D** in the form of lines. In this manner, when the second bending protective layer **BPL** is applied along the line-shaped opening **L** formed by the anti-delamination structures **D** having the inverted taper shape which are disposed adjacent to each other in the form of lines, the contact area between the second bending protective layer **BPL** and the outer inclined surface **DP1** of the anti-delamination structures **D** arranged in the line shape can be increased. As a result, it is possible to increase the resistance against the force to delaminate the second bending protective layer **BPL**. In addition, even if a part of the second bending protective layer **BPL** applied in the line-shaped opening **L** is delaminated, it is possible to prevent delamination of the other part of the anti-delamination structures **D**.

(157) FIG. **21** is a cross-sectional view of anti-delamination structures **D** according to an embodiment of the disclosure.

(158) In the embodiment of FIG. **21**, a part of a bending inorganic layer **290** of an anti-delamination structure **D** may further include a crack **290c**.

(159) Since the bending inorganic layer **290** is located in the panel bending region **BR**, it is exposed to bending stress, and thus cracks **290c** may occur in a part of the bending inorganic layer **290** as shown in FIG. **21**. Usually, when cracks are formed in an inorganic layer, they may propagate along the inorganic layer and may affect the display quality. However, when cracks **290c** are generated in the bending inorganic layer **290**, propagation can be suppressed by the shape of the protrusion pattern **126b_2** thereunder. In addition, when the bending inorganic layer **290** is formed separately from the layers of the display area **DPA**, even if the cracks **290c** propagate, they cannot affect the layers of the display area **DPA**.

(160) On the other hand, since the second bending protective layer **BPL** is formed even in the cracks **290c** formed in the bending inorganic layer **290**, the adhesion between the second bending protective layer **BPL** and the anti-delamination structures **D** can be even enhanced due to an increased contact area between the second bending protective layer **BPL** and the bending inorganic layer **290** at the cracks **290c**. Therefore, the cracks **290c** formed in the bending inorganic layer **290**

can help suppress the delamination of the second bending protective layer BPL.

(161) Hereinafter, a method of fabricating (or providing) a display device **1** will be described in detail with reference to FIGS. **22** to **25**.

(162) FIGS. **22** to **25** are cross-sectional views for illustrating structures and processes in the method of fabricating (or providing) a display device **1** according to an embodiment of the disclosure.

(163) Referring to FIG. **22**, an intermediate structure is prepared, in which a buffer layer **105**, a semiconductor layer **110**, a first insulating layer **121**, a first conductive layer **130**, a second insulating layer **122**, a second conductive layer **140**, a third insulating layer **123**, a bending insulating layer **127**, a third conductive layer **150**, a fourth insulating layer **124**, a fourth conductive layer **160**, a fifth insulating layer **125** and a fifth conductive layer **170** are sequentially stacked on one another on the substrate **100**. A variety of methods for forming such an intermediate structure are well known in the art and thus are not described herein.

(164) Subsequently, an organic material layer **126p** for a sixth insulating layer **126** is disposed on the fifth conductive layer **170**.

(165) Subsequently, the organic material layer **126p** for the sixth insulating layer **126** is patterned by performing exposure and development using a halftone mask HFM. The halftone mask HFM includes a light-blocking portion BL, a first light-transmitting portion HT, and a second light-transmitting portion TR having a transmittance greater than that of the first light-transmitting portion HT. An example where the organic material layer **126p** for the sixth insulating layer **126** includes a negative photosensitive material will be described. The light-blocking portion BL is placed in line with a second region R2 in which the opening of the pixel-defining layer **126a_1** of the display area DPA is to be formed. The first light-transmitting portion HT is placed in line with a first region R1 in which the pixel-defining layer **126a_1** of the display area DPA and the base **126b_1** of the non-display area NDA are to be formed. The halftone mask HFM is placed such that the second light-transmitting portion TR is in line with the third region R3 in which the spacer **126a_2** of the display area DPA and the protrusion pattern **126b_2** of the non-display area NDA are to be formed. The organic material layer **126p** for the sixth insulating layer **126** is exposed to light using the halftone mask HFM.

(166) Subsequently, the organic material layer **126p** for the sixth insulating layer **126** is developed after it is exposed to light. As a result, the pattern shape of the six insulating layer **126** including a pixel partition wall **126a** including the pixel-defining layer **126a_1** and the spacer **126a_2**, and a first bending protective layer **126b** including the base **126b_1** and the protrusion pattern **126b_2** is completed, as shown in FIG. **23**. By performing the process using a halftone mask HFM in this manner, the pixel partition wall **126a** including the pixel-defining layer **126a_1** and the spacer **126a_2**, and the first bending protective layer **126b** including the base **126b_1** and the protrusion pattern **126b_2** can be formed simultaneously via the single process, so that the process efficiency can be increased.

(167) Subsequently, referring to FIG. **24**, an emissive layer **128**, a sixth conductive layer **180**, a first inorganic layer **191**, an organic layer **192**, a second inorganic layer **193**, an adhesive layer **194**, and a polarization layer POL are formed on the display area DPA by any of a variety of methods well known in the art.

(168) Subsequently, referring to FIG. **25**, a bending inorganic layer **290** is formed on the first bending protective layer **126b** of the non-display area NDA. The bending inorganic layer **290** is formed by any of various CVD deposition techniques such as plasma enhanced chemical vapor deposition (PECVD), atmospheric pressure CVD (APCVD), and low-pressure CVD (LPCVD). As the bending inorganic layer **290** is formed, the anti-delamination structures D including the protrusion pattern **126b_2** of the first bending protective layer **126b** and the bending inorganic layer **290** is completed. The bending inorganic layer **290** has an outer inclined surface DP1 in an inverted taper shape on the protrusion pattern **126b_2**, which will be described in detail with reference to

FIG. 26.

(169) Subsequently, the second bending protective layer BPL is applied on the bending inorganic layer **290** to complete the display device **1** as shown in FIG. 3.

(170) FIGS. 26A to 26C are cross-sectional views illustrating a process of depositing a bending inorganic layer **290** by chemical vapor deposition according to an embodiment.

(171) Referring to FIG. 26A, according to an embodiment of the disclosure, the bending inorganic layer **290** is disposed on the base **126b_1** and the protrusion pattern **126b_2** of the first bending protective layer **126b**, by chemical vapor deposition (CVD). In this step, the bending inorganic layer **290** is formed conformally on the surface shape of the first bending protective layer **126b** with a thin thickness.

(172) In the chemical vapor deposition process, deposition and growth may be performed isotropically. Specifically, if the deposition process is continued, a thin layer may be grown in the lateral direction of the protrusion PT and away from the protrusion PT. Such thin layers as shown between the bending inorganic layer **290** and the first bending protective layer **126b** in FIGS. 26B and 26C, which are grown in the lateral direction at the upper portion of the protrusion PT may narrow the entrance of the opening W at an upper side to provide the protruding portion **290a**, and thus the maximum thickness increase at the protruding portion **290a** may work as a deposition shadow that hinders deposition. This becomes larger as deposition and growth continue, and accordingly, the outer inclined portion of the bending inorganic layer **290** can have the inverted taper shape as shown in FIGS. 26B and 26C. As a result, as shown in FIG. 26C, a difference in the thickness of the bending inorganic layer **290** within the opening W occurs, and the opening width of the opening W may become narrower toward the upper side. In an embodiment, a minimum opening width of the opening W may be defined by protruding portions **290a** opposing each other at the upper side of the opening W (e.g., entrance of the opening W). That is, the anti-delamination protrusion structure has an inverted taper shape with a maximum dimension of the protrusion structures at a distal end thereof.

(173) FIG. 27 is a view showing a force acting in a process of depositing a bending inorganic layer **290** according to an embodiment.

(174) Referring to FIG. 27, when the bending inorganic layer **290** is deposited on the protrusion PT, a tensile stress may act between inorganic materials. When such tensile stress acts, the inorganic material is maximally stretched in the horizontal direction by a first force F1 and in the vertical direction by a second force F2. In addition, the first force F1 in the horizontal direction and the second force F2 in the vertical direction overlap each other at the edge of the bending inorganic layer **290** deposited on the upper surface of the protrusion PT. As a result, the forces combine to act in the direction of forming the protruding portion **290a** (inclined arrows in FIG. 27).

(175) In addition, as the first force F1 in the horizontal direction and the second force F2 in the vertical direction overlap each other at the corners C at opposing sides of the upper surface of the bending inorganic layer **290** deposited lowest in the opening W, the compressive force acts, to form the inverted taper structure.

(176) As such, due to the deposition shadow action of the inorganic material and/or the action of tensile stress between the inorganic materials described above with reference to FIG. 26, it is possible to form the outer inclined surface DP1 in the inverted taper shape by the bending inorganic layer **290**, even when the protrusion PT underlying the bending inorganic layer **290** does not have the inverted taper shape.

(177) In concluding the detailed description, those skilled in the art will appreciate that many variations and modifications can be made to the embodiments without substantially departing from the principles of the invention. Therefore, the disclosed embodiments of the invention are used in a generic and descriptive sense only and not for purposes of limitation.

Claims

1. A display device comprising: a substrate comprising a display area and a bending region which is adjacent to the display area; a pixel partition wall layer on the substrate and comprising a pixel-defining layer in the display area; a first bending protective layer on the substrate and comprising a protrusion pattern in the bending region, the protrusion pattern comprising a base, and a plurality of protrusions which are integral with the base and each extend from the base; and a bending inorganic layer on the protrusion pattern of the first bending protective layer, in the bending region, the bending inorganic layer including an outer surface having an inverted taper shape with respect to the substrate.
2. The display device of claim 1, wherein the pixel partition wall layer in the display area and the first bending protective layer in the bending region include a same material.
3. The display device of claim 2, wherein the pixel partition wall layer further comprises a spacer which is on the pixel-defining layer and integral with the pixel-defining layer, each of the protrusion pattern and the spacer has a height taken from the substrate, and the height of the protrusion pattern is equal to the height of the spacer.
4. The display device of claim 1, further comprising in the bending region, a second bending protective layer on the first bending protective layer.
5. The display device of claim 4, wherein the protrusion pattern of the first bending protective layer includes an upper portion, and a lower portion which is closer to the substrate than the upper portion, and in a direction along the substrate, the bending inorganic layer at the upper portion of the protrusion pattern extends further from the protrusion pattern than the bending inorganic layer at the lower portion of the protrusion pattern.
6. The display device of claim 5, wherein the protrusion pattern comprises a base, and a plurality of protrusions which are spaced apart from each other with a portion of the base therebetween, and the bending inorganic layer at the upper portion of the protrusion pattern, overlaps the portion of the base, to define a shadow area between the bending inorganic layer at the upper portion of the protrusion pattern and the portion of the base.
7. The display device of claim 6, wherein the shadow area is filled with the second bending protective layer.
8. The display device of claim 1, further comprising in the display area, an encapsulation layer on the pixel-defining layer, wherein the encapsulation layer comprises a first inorganic layer, an organic layer on the first inorganic layer, and a second inorganic layer on the organic layer.
9. The display device of claim 8, wherein the bending inorganic layer comprises a same material as the first inorganic layer or the second inorganic layer of the encapsulation layer.
10. The display device of claim 1, wherein in the bending region, the protrusion pattern of the first bending protective layer comprises a plurality of protrusions spaced apart from each other and each comprising an outer surface having the inverted taper shape.
11. A display device comprising: a substrate comprising a display area including a plurality of pixels, and a bending region which is adjacent to the display area; a polarization layer in the display area and covering the plurality of pixels; and in the bending region: an anti-delamination protrusion structure having an outer surface in an inverted taper shape; the outer surface in the inverted taper shape defined by an upper surface and side surfaces of the anti-delamination protrusion structure; and a bending protective layer on the anti-delamination protrusion structure and in contact with the upper surface and the side surfaces of the outer surface of the anti-delamination protrusion structure, wherein the bending protective layer is in contact with the polarization layer.
12. The display device of claim 11, wherein the anti-delamination protrusion structure comprises an organic protrusion and a bending inorganic layer which is on the organic protrusion.
13. The display device of claim 12, wherein the organic protrusion includes side surfaces extended

normal with respect to the substrate or extended inclined with respect to the substrate, and the bending inorganic layer extends along the side surfaces of the organic protrusion to have an inverted taper inclination.

14. A method of providing a display device, the method comprising: providing a substrate comprising a display area, and a bending region which is adjacent to the display area; providing a pixel partition wall layer on the substrate, in the display area, the pixel partition wall layer comprising a pixel-defining layer and a spacer which is on the pixel-defining layer; and providing in the bending region: a first bending protective layer on the substrate and comprising a protrusion pattern; and a bending inorganic layer on the protrusion pattern of the first bending protective layer, the bending inorganic layer having an inverted taper shape with respect to the substrate, wherein the providing of the pixel-defining layer and the spacer of the pixel partition wall layer, and the providing of the protrusion pattern of the first bending protective layer, are simultaneous.

15. The method of claim 14, wherein the providing of the bending inorganic layer on the protrusion pattern comprises providing the inverted taper shape by chemical vapor deposition.

16. The method of claim 14, wherein the protrusion pattern of the first bending protective layer comprises a plurality of protrusions, and each of the protrusions among the plurality of protrusions has a side surface which is a vertical with respect to the substrate or inclined with respect to the substrate.

17. The method of claim 14, further comprising, providing in the bending region, a second bending protective layer facing the first bending protective layer with the bending inorganic layer therebetween.

18. The method of claim 14, wherein each of the protrusion pattern in the bending region, and the spacer in the display area, has a height taken from the substrate, and the height of the protrusion pattern is equal to the height of the spacer.
