



US012392139B2

(12) **United States Patent**
Courey et al.

(10) **Patent No.:** **US 12,392,139 B2**
(45) **Date of Patent:** ***Aug. 19, 2025**

(54) **TILE WITH IMITATION GROUT LINE**

(71) Applicant: **Quickstyle Industries Inc.**, Montreal
(CA)

(72) Inventors: **Stephen Courey**, Quebec (CA);
Michele Alfieri, Quebec (CA)

(73) Assignee: **QUICKSTYLE INDUSTRIES, INC.**,
Montreal (CA)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 425 days.

This patent is subject to a terminal dis-
claimer.

(21) Appl. No.: **17/505,165**

(22) Filed: **Oct. 19, 2021**

(65) **Prior Publication Data**

US 2022/0213693 A1 Jul. 7, 2022

Related U.S. Application Data

(63) Continuation-in-part of application No. 17/002,418,
filed on Aug. 25, 2020, now Pat. No. 11,149,442,
(Continued)

(51) **Int. Cl.**
E04F 15/02 (2006.01)
B32B 3/06 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **E04F 15/02033** (2013.01); **B32B 3/06**
(2013.01); **B32B 3/263** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC E04F 15/02033; E04F 15/02038; E04F
15/107; E04F 2201/0153; E04F 2201/023;
(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,242,390 A 12/1980 Nemeth
5,437,934 A 8/1995 Witt et al.
(Continued)

FOREIGN PATENT DOCUMENTS

AU 2013335260 5/2012
AU 2015391767 A1 1/2017
(Continued)

OTHER PUBLICATIONS

Aquaplink, WPC CLIC Vinyl Floor Plank, Jan. 1, 2018.


Primary Examiner — Catherine A. Simone

(74) *Attorney, Agent, or Firm* — Malloy & Malloy, PL;
Jennie S. Malloy

(57) **ABSTRACT**

A tile for use as a covering on a floor, wall, or other surface comprising a top section disposed on a rigid core layer, wherein the top section comprises in some embodiments a veneer layer, or another layer or coating of material, such as polyurethane, upon which at least one design element may be imparted, such as through printing processes. The inventive tile in some embodiments described herein further comprises an exposed portion, or a plurality thereof, configured to provide a highly realistic imitation of a grout line. The inventive tile may also comprise at least one interconnecting mechanism, wherein such interconnecting mechanism may be formed on the same side of the tile as the exposed portion. In at least one embodiment, the layer or coating of material is disposed in covering relation to the exposed portion, and alternatively, a protective layer may instead be applied onto the exposed portion.

8 Claims, 47 Drawing Sheets



Related U.S. Application Data

which is a continuation of application No. 16/358,241, filed on Mar. 19, 2019, now abandoned, which is a continuation-in-part of application No. 16/196,974, filed on Nov. 20, 2018, now Pat. No. 10,544,595, which is a continuation-in-part of application No. 15/950,046, filed on Apr. 10, 2018, now Pat. No. 10,132,088, which is a continuation-in-part of application No. 15/454,650, filed on Mar. 9, 2017, now Pat. No. 9,938,726.

- (60) Provisional application No. 62/380,122, filed on Aug. 26, 2016.

(51) Int. Cl.

B32B 3/26 (2006.01)

B32B 27/20 (2006.01)

B32B 27/30 (2006.01)

E04F 15/10 (2006.01)

(52) U.S. Cl.

CPC **B32B 27/20** (2013.01); **B32B 27/304** (2013.01); **E04F 15/02038** (2013.01); **E04F 15/107** (2013.01); **B32B 2264/10** (2013.01); **B32B 2307/412** (2013.01); **B32B 2307/72** (2013.01); **B32B 2419/04** (2013.01); **E04F 2201/0153** (2013.01); **E04F 2201/023** (2013.01); **E04F 2201/043** (2013.01)

(58) Field of Classification Search

CPC **E04F 2201/043**; **B32B 3/06**; **B32B 3/263**; **B32B 27/20**; **B32B 27/304**; **B32B 2307/412**; **B32B 2307/72**; **B32B 2419/04**
See application file for complete search history.

(56)**References Cited**

U.S. PATENT DOCUMENTS

6,363,677	B1	4/2002	Chen et al.	10,407,906	B2	9/2019	Quanshan et al.
6,497,079	B1	12/2002	Pletzer et al.	10,544,595	B2	1/2020	Courey et al.
6,536,178	B1	3/2003	Palsson et al.	10,968,640	B2	4/2021	Dai
6,617,009	B1	9/2003	Chen et al.	11,041,317	B2	6/2021	Tong
6,647,690	B1	11/2003	Martensson	11,060,298	B2	7/2021	Liu et al.
6,880,307	B2	4/2005	Schwitte et al.	11,149,442	B2*	10/2021	Courey B32B 27/304
7,211,310	B2	5/2007	Chen et al.	2001/0041256	A1	11/2001	Heilmayr
7,261,947	B2	8/2007	Reichwein et al.	2002/0092263	A1	7/2002	Schulte
7,288,310	B2	10/2007	Hardwick	2002/0139082	A1	10/2002	DeFord et al.
7,458,191	B2	12/2008	Stone	2003/0091780	A1	5/2003	Andersson
7,544,423	B2	6/2009	Horton	2003/0138618	A1	7/2003	Courttoy et al.
7,763,345	B2	7/2010	Chen et al.	2004/0146695	A1	7/2004	Hardwick
8,021,741	B2	9/2011	Chen et al.	2004/0211144	A1	10/2004	Stanchfield
8,234,829	B2	8/2012	Thiers et al.	2005/0003160	A1	1/2005	Chen et al.
8,363,677	B2	1/2013	Seki et al.	2005/0079323	A1	4/2005	Miller et al.
8,689,513	B2	4/2014	Windmoller	2006/0070332	A1	4/2006	Palsson et al.
8,720,144	B2	5/2014	Keane	2006/0159891	A1	7/2006	Viet et al.
8,857,127	B2	10/2014	Windmoller	2006/0272252	A1	12/2006	Moller, Jr.
8,875,465	B2	11/2014	Martensson	2006/0283118	A1	12/2006	Moller, Jr.
8,956,714	B2	2/2015	Vermeulen	2007/0125021	A1	6/2007	Thiers et al.
9,127,459	B2	9/2015	Litral	2008/0115437	A1	5/2008	Bordener
9,156,233	B2	10/2015	Dossche et al.	2009/0031658	A1	2/2009	Moller, Jr. et al.
9,193,137	B2	11/2015	Dossche et al.	2009/0038254	A1	2/2009	Steele et al.
9,200,460	B2	12/2015	Cappelle	2009/0107071	A1	4/2009	Starke
9,234,357	B2	1/2016	Dossche et al.	2009/0155612	A1	6/2009	Pervan et al.
9,783,996	B2	10/2017	Pervan et al.	2010/0055420	A1	3/2010	Vermeulen
9,938,726	B2	4/2018	Alfieri et al.	2010/0319294	A1	12/2010	Courey et al.
9,988,821	B2	6/2018	Rose et al.	2011/0067340	A1	3/2011	Shapiro et al.
10,132,088	B2	11/2018	Courey et al.	2011/0146189	A1	6/2011	Courey
10,202,768	B2	2/2019	Doehring	2011/0167744	A1	7/2011	Whispell et al.
10,208,490	B2	2/2019	Meersseman et al.	2011/0296780	A1	12/2011	Windmoller
10,233,655	B2	3/2019	Meersseman et al.	2011/0300392	A1	12/2011	Vermeulen
10,233,656	B2	3/2019	Courey et al.	2012/0240502	A1	9/2012	Wilson et al.
10,335,990	B2	7/2019	Dai	2012/0291387	A1	11/2012	Keane
10,343,381	B2	7/2019	Troendle et al.	2013/0104486	A1	5/2013	Windmoller
				2013/0111843	A1	5/2013	Litral
				2014/0109507	A1	4/2014	Dossche et al.
				2014/0147641	A1	5/2014	Vermeulen
				2014/0157695	A1	6/2014	Windmoller
				2014/0227484	A1	8/2014	Sung et al.
				2014/0290158	A1	10/2014	Meersseman
				2014/0329062	A1	11/2014	Song
				2015/0072102	A1	3/2015	Dossche et al.
				2015/0096256	A1	4/2015	Lam et al.
				2015/0147531	A1	5/2015	Anspach
				2015/0159379	A1	6/2015	Meersseman et al.
				2015/0165735	A1	6/2015	Joung
				2015/0167320	A1	6/2015	Meersseman et al.
				2015/0239230	A1	8/2015	Vermeulen
				2015/0337543	A1	11/2015	Dossche et al.
				2016/0083965	A1	3/2016	Baert et al.
				2016/0145876	A1	5/2016	Dossche et al.
				2016/0153190	A1	6/2016	Doehring
				2016/0200034	A1	7/2016	Quanshan et al.
				2016/0207835	A1	7/2016	Zheng
				2016/0229161	A1	8/2016	Zhang et al.
				2016/0347085	A1	12/2016	Cloots et al.
				2016/0348368	A1	12/2016	Godfrey et al.
				2016/0348369	A1	12/2016	Godfrey et al.
				2016/0361891	A1	12/2016	Tang
				2016/0375718	A1	12/2016	Van Garsse et al.
				2017/0009462	A1	1/2017	Muehlebach
				2017/0021598	A1	1/2017	Chen
				2017/0044778	A1	2/2017	Brickner et al.
				2017/0136674	A1	5/2017	Chen et al.
				2017/0136731	A1	5/2017	Rose et al.
				2017/0152666	A1	6/2017	Li et al.
				2017/0356130	A1	12/2017	Guyot et al.
				2017/0368760	A1	12/2017	Troendle et al.
				2018/0044925	A1	2/2018	Koh et al.
				2018/0058077	A1	3/2018	Alfieri et al.
				2018/0106039	A1	4/2018	Courey et al.
				2018/0142478	A1	5/2018	Xu
				2018/0171644	A1	6/2018	Zhang
				2018/0207918	A1	7/2018	Dai
				2018/0298621	A1	10/2018	Courey et al.
				2018/0298622	A1	10/2018	Courey et al.
				2019/0001543	A1	1/2019	Dai
				2019/0003189	A1	1/2019	Dohring

(56)

References Cited

U.S. PATENT DOCUMENTS

2019/0085566	A1	3/2019	Lingg
2019/0145109	A1	5/2019	Esbelin
2019/0169858	A1	6/2019	Courey et al.
2019/0283272	A1	9/2019	Zhang et al.
2019/0283302	A1	9/2019	Troendle et al.
2019/0283364	A1	9/2019	Ting
2019/0316363	A1	10/2019	Courey et al.
2019/0316364	A1	10/2019	Wang et al.
2019/0330860	A1	10/2019	Wang et al.
2019/0352915	A1	11/2019	Dai
2019/0368204	A1	12/2019	Wang et al.
2020/0131783	A1	4/2020	Liu et al.
2020/0318362	A1	10/2020	Tong

FOREIGN PATENT DOCUMENTS

AU	2017315241	12/2019
CA	3004243	8/2022
CN	2410321	12/2000
CN	2690449	4/2005
CN	100462398	1/2007
CN	1911997	2/2007
CN	1912313	2/2007
CN	201024633	2/2008
CN	100419019	9/2008
CN	101365852	2/2009
CN	101400866	4/2009
CN	101698749	4/2010
CN	101767362	7/2010
CN	101955614	1/2011
CN	101614068	11/2011
CN	202324474	11/2011

CN	202144660	2/2012
CN	203546560	4/2014
CN	203961205	11/2014
CN	204386113	6/2015
CN	204715139	10/2015
CN	105200897	12/2015
CN	103397767	1/2016
CN	204940032	1/2016
CN	204940072	1/2016
CN	105297578	2/2016
CN	205077362	3/2016
CN	205100047	3/2016
CN	205115955	3/2016
CN	106193518	12/2016
CN	106193520	12/2016
CN	106193530	12/2016
CN	106193531	12/2016
CN	106320137	1/2017
CN	205990729	3/2017
CN	205990730	3/2017
CN	205990732	3/2017
CN	205990733	3/2017
CN	107208362	9/2017
CN	107794819	3/2018
CN	109808395 A	1/2019
CN	211112973	7/2020
EP	2202056	6/2010
EP	3359760	6/2022
WO	WO2009007735	1/2009
WO	WO2013117653	8/2013
WO	WO2016113378	7/2016
WO	WO2016142647	9/2016
WO	WO2018037270	3/2018
WO	WO2018162992	9/2018

* cited by examiner

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7B




FIG. 8




FIG. 9





FIG. 10



٢٠١١




FIG. 12




FIG. 13




FIG. 14




FIG. 15A




FIG. 15B




FIG. 16A




FIG. 16B




FIG. 17A




FIG. 17B




FIG 18




FIG 19




FIG 20




FIG 21




FIG 22




FIG 23




FIG 24




FIG 25




FIG 26




FIG 27





FIG 28








FIG. 29








FIG. 32

FIG. 33A




FIG. 33B




FIG. 34




FIG. 35A




FIG. 35B




FIG. 36A




FIG. 36B




FIG. 37




FIG. 38





FIG. 39






FIG. 41




FIG. 42





FIG. 43



TITLE WITH IMITATION GROUT LINE

CLAIM OF PRIORITY

This application is a Continuation-in-Part of a currently pending patent application having Ser. No. 17/002,418, filed on Aug. 25, 2020 and set to issue as U.S. Pat. No. 11,149,442 on Oct. 19, 2021, which is a continuation of currently pending patent application having Ser. No. 16/358,241 and a filing date of Mar. 19, 2019, which itself is a Continuation in Part (CIP) of a patent application having Ser. No. 16/196,974 and a filing date of Nov. 20, 2018, which claims priority to a Continuation in Part (CIP) patent application having Ser. No. 15/950,046 and a filing date of Apr. 10, 2018 and which matured into U.S. Pat. No. 10,132,088 on Nov. 20, 2018, which in turn claimed priority to a patent application having Ser. No. 15/454,650 and a filing date of Mar. 9, 2017, which matured into U.S. Pat. No. 9,938,726 on Apr. 10, 2018, which in turn claimed priority to a U.S. provisional patent application having Ser. No. 62/380,122 and a filing date of Aug. 26, 2016. In addition, the present application claims priority to a currently pending Continuation in Part (CIP) patent application having Ser. No. 15/949,979 and a filing date of Apr. 10, 2018, which is set to issue as U.S. Pat. No. 10,233,656 on Mar. 19, 2019, which also claims priority to the above-referenced patent application having Ser. No. 15/454,650 and a filing date of Mar. 9, 2017, which matured into U.S. Pat. No. 9,938,726. All of the foregoing applications and patents are incorporated herein by reference.

BACKGROUND OF THE INVENTION

Field of the Invention

The present invention is directed to a tile, such as a flooring tile, which in most embodiments is made entirely from synthetic materials and having an appearance of real marble, stone, ceramic or wood, and which offers a highly realistic looking but imitation grout line formed along the length of one or more of its sides. The inventive tile comprises at least a top layer and a core layer, and during the manufacturing process, at least a portion of the top layer is formed so as to define an exposed portion along at least one side of the tile, which extends outwardly below and away from the top surface of the tile. In some embodiments, the top layer may comprise only a veneer layer, or one or more coatings of material with the appearance of wood or stone applied by printing thereon. The exposed portion of the tile may comprise a textured surface or be otherwise structured to closely resemble the look and feel of an actual grout line, and further, may include a colorant to correspond with the overall intended color of the resulting tile. In one or more additional embodiments, the inventive tile includes a protective section structured to avoid or reduce staining of the exposed portion that closely resembles an actual grout line.

Description of the Related Art

During the construction of a home, building or other structure, there will almost always be an unfinished floor surface such as a slab of concrete, a wood sub-structure or the like, which needs to be finished to offer a more appealing and/or polished appearance. It is also true that there will almost always be an unfinished wall surface made of a wood substructure, having dry wall affixed thereto, or another substructure such as concrete or concrete block. In many cases, tiles will be used to finish either a floor surface or a

wall surface, with the tiles often being made of real marble or stone, or depending on budgetary constraints, of porcelain or ceramic. Traditionally, such tiles are secured to the unfinished floor slab or wall surface using a cement-like mixture, with one or more tiles disposed closely next to each other, and leaving a small separation between the sides of adjacent tiles. Forming this separation between tiles is often tedious and requires the use of spacers to ensure uniformity and alignment of the tiles. Also, this separation will later be filled with a grout mixture as part of the installation process, which creates a "grout line" around the sides of the tiles. In general, the process of installing tile and creating the grout line involves a significant amount of time, which adds to the labor and overall cost of the project.

Over the last several years, flooring products and tiles have been made from synthetic materials and configured to imitate the look of a real tile of marble, stone or ceramic. For example, laminate and vinyl flooring products are known, including some that imitate the look of real stone, marble, or ceramic tiles. These flooring products create an optical or visual illusion so that the surface of the tile looks like real stone, marble or ceramic or even like real wood flooring. Traditionally, however, such flooring products are manufactured so as to require that the individual tiles be installed directly next to each other, often in abutting relation, although some of these products are installed with a slight separation between them to facilitate installation on uneven floor surfaces. While this slight separation may be observable and in some cases may appear as a small seam or even as a micro groove, these types of known tiles do not offer any structure to represent or closely resemble the look and feel of a real grout line. This is also true of existing imitation flooring products having an interconnecting mechanism to facilitate installation, such as correspondingly disposed "tongue" and "groove" structures formed along a side of a tile. Additionally, some laminate flooring planks are known to offer an optical illusion of having a grout line, but in reality, the seams of such flooring planks and/or tiles are completely flat and have imitation grout lines drawn and shaded on the edges by an artist to give the impression of depth.

It would therefore be ideal if a tile were made so as to be formed from synthetic materials so as to offer the appearance of genuine wood or stone, and also so as to reliably include an artificial but highly realistic looking grout line. Any such tile would preferably also include a top layer and a rigid core layer, at least partially or fully into which the artificial grout line is formed.

While some flooring products or tiles exist, none are believed to have ever featured one with a top layer of material, such as but not limited to a polyvinyl chloride (PVC) material having an optimal density or other characteristics so that a portion thereof can be exposed during the manufacturing process to form an imitation grout line with a highly realistic look and feel of an actual grout line. Furthermore, no such tiles or flooring products are believed to have ever featured a top layer of material, such as polyvinyl chloride (PVC), combined with a colorant during the manufacturing process so as to provide a variety of colors for the imitation grout line that will match with or closely correspond to the overall color of the resulting tile.

Additionally, of the known flooring products or tiles that exist, none are believed to feature a rigid core layer formed of a densified foam material or a stone plastic composite material and having optimal density ranges or other characteristics that render it sufficiently rigid and durable for a wide variety of applications.

Also, and even though some of the existing imitation flooring products have correspondingly disposed “tongue” and “groove” structures formed along a side of a tile, there are drawbacks associated with these when it is desired to use such flooring products on a wall surface, as opposed to a floor surface. More specifically, the installation process for such products on a vertical surface, such as a wall, is cumbersome and further, remains labor intensive and therefore costly. As such, there is room for improvements in the structuring of such tiles for interconnection and installation on a vertical surface, such as a wall.

Accordingly, it would be beneficial if an improved tile or flooring product made from synthetic materials were developed, such as but not limited to one having a core layer made at least in part from a densified foam material, or from a stone plastic composite material, so as to be sufficiently rigid and durable for a wide variety of applications, and further, which is capable of being easily and quickly installed, even on a vertical surface, such as a wall. Additionally, if any such improved tile or flooring product were developed, it would also be beneficial if it could be made to include a top layer of material, such as but not limited to a polyvinyl chloride (PVC) material, that is capable of being readily formed during the manufacturing process to achieve a desired appearance, such as the look of natural wood, stone, etc. and at least partially into or through which, an artificial but realistic looking grout line could be formed.

SUMMARY OF THE INVENTION

The present invention is intended to present a solution to these and other needs which remain in this field of art, and as such, is directed to a tile, primarily but not exclusively intended for use in flooring applications, that imitates the look and feel of a real tile surface such as stone, ceramic, or marble, and the like, including the look of wood flooring, and further, which is formed from material(s) that can be made in a variety of different colors and designs. The present invention is also directed, however, to a tile that is structured to have an imitation grout line, but with a highly realistic look and feel similar to an actual grout line, formed on or substantially along at least one side or edge of the tile. Additionally, the tile of the present invention may be manufactured in different dimensions of varying length and width, and may also be produced in a variety of shapes such as, but not limited to, rectangular, square, hexagonal, or octagon, and others. As will also be described with regard to at least one or more other embodiments, the tile of the present invention may also be manufactured so as to include a very thin veneer layer of genuine wood or stone, or top layer of another material or coating of material.

As will become clear from the description which follows, the tile of the present invention comprises at least a top layer and a core layer. The top layer in most embodiments, but not all, comprises generally a layer made from a vinyl composite material, including a synthetic plastic polymer such as, but not limited to, polyvinyl chloride (PVC). However, in some embodiments described herein, particularly wherein the core layer of the inventive tile is made from a stone plastic composite (SPC), which may also be referred to at times as a stone polymer composite (SPC), a top layer or section comprising a polyvinyl chloride (PVC) material is not needed, while in one or more other embodiments, a top layer or section may be included which may comprise a decorative layer and a wear layer. Additionally, it should be noted the core layer of at least one embodiment of the present invention may comprise yet additional types of material

compositions, provided such material composition possesses sufficiently rigid properties for use in flooring applications. Accordingly, such a core layer may comprise various densities, various amounts of polyvinyl chloride (PVC) or other like synthetic plastic polymers, and/or various amounts of calcium carbonate or other like chemical compounds.

Even further, the top layer may instead comprise alternate materials. For instance, as previously stated, the top layer and/or top section may comprise a veneer layer, such as a very thin layer of genuine wood or stone. Alternatively, the top layer, whether as a veneer layer or other layer of material may instead comprise a coating of material, such as but not limited to an enamel coating, which may itself comprise a fill coat or any other like topically applied material, such as an acrylic and/or polycrylic coating, or a coating of polyurethane and/or ethoxyline resin. In such embodiments, the coating of material, such as an enamel coating, may be applied to or disposed directly onto the core layer and may comprise a clear and/or a colored appearance, such as white, beige, grey, black, some combination thereof, or otherwise. In at least one embodiment of the present invention, the coating of material, such as an enamel coating, may be applied onto the core layer when in liquid form, such as through one or more spraying processes. And, in embodiments wherein the core layer is naturally porous due to its chemical composition, such as when the core layer is comprised of a stone plastic composite material and/or a stone polymer composite material, the coating of material, such as an enamel coating, may be predisposed to seal such inherent porosity, thereby filling in any gaps and/or crack inherent in the core layer. In this sense, it may be understood such top layer and/or section need not comprise an actual layer of solid material adhesively joined to the core layer; but rather, may merely comprise a topical liquid applied onto the core layer, before subsequently being allowed to dry.

It may be understood that once applied to the core layer, the coating of material, such as but not limited to an enamel coating, may function as a primer of sorts, wherein the surface of the core layer is rendered smooth, and suitable for the application of at least one design element thereon. As further described herein, such at least one design element may comprise, for instance, textures, grooves, impressions, undulations, color or graphical designs, or any other feature now known or hereafter developed, and may be applied to the tile by printing thereon. For instance, such at least one design element may be configured or printed to imitate the look and feel of real materials, such as real stone or marble, or real wood.

In most embodiments, but not all, the top layer of the inventive tile comprises at least one PVC layer, as described above. However, in at least one preferred embodiment, the top layer additionally comprises both a wear layer and/or a decorative layer. Also, the top layer of the tile, and particularly the wear layer in said one or more embodiments, is formed to have a selected thickness depending upon the intended use of the tile such as residential, light contract, heavy commercial, or other type of use. Moreover, the density of the polyvinyl chloride (PVC) layer material is such that the inventive tile(s) may be readily modified during the manufacturing process to achieve the desired effect of offering a highly realistic looking grout line when viewed by a person standing on or near the floor surface. Also during the manufacturing process, the top surface of the tile, defined by the top layer and specifically, by the wear layer in one or more embodiments, may be pressed or otherwise modified to achieve a variety of textured surfaces

5

thereon, which help to provide the tile with an appearance of real marble, stone, ceramic or of a real wood surface or other natural textures. The core layer of the inventive tile comprises a rigid and waterproof material. More specifically, the core layer comprises a “densified foam” material in several embodiments. Also, the material composition and density range of the densified foam ensure that the core layer, and consequently the tile(s), is/are both relatively lightweight and yet sufficiently rigid and durable for flooring applications. In some cases, the core layer comprising a densified foam material may be referred to as a Wood Plastic Composite (WPC), but the composition of the core layer should not be construed as being limited to this. Additionally, the core layer may have a smooth texture. Further, the core layer may comprise one or more sublayers that serve as an underlayment. These sublayers may be made from other materials such as, but not limited to, laminate foil, cork, foam, or ethyl vinyl acetate.

The inventive tile also comprises an exposed portion that extends outwardly from and along the length of at least one side of the tile that is structured to simulate a grout line. The exposed portion is associated with a sidewall and defines a gap that preferably extends uniformly and substantially along the side of the tile. The exposed portion additionally comprises a textured surface structured to closely simulate the appearance of a real grout line. The exposed portion may also be formed on one or more layers of the inventive tile so as to have realistic looking dimensions and coloring. As illustrated in several of the Figures, the exposed portion is formed along at least one side of the inventive tile, but in other embodiments, may be disposed along more than one side or even along all sides of the tile. This exposed portion is preferably formed on the tile during the manufacturing process, as opposed to during installation. During the manufacturing process, a tool, such as but not limited to a knife, cutting blade(s) and the like, may be configured and used to remove a portion of the top surface of the tile uniformly along at least one selected side thereof, or even across a central or middle portion thereof, and will expose at least a portion of the top layer of the tile, and in some embodiments may expose a portion of the core layer. Additionally, the knife, cutting blade(s) or other tool may also modify the exposed portion, such as by further cutting and/or profiling of it so as to provide the textured appearance that closely simulates the look and feel of a real grout line.

In one or more additional embodiments, the present invention further includes a protective section disposed between a top section and a core layer of the tile, which includes an exposed portion formed to closely resemble a real grout line, as described herein. The protective section is structured to at least partially reduce and/or avoid staining of the exposed portion comprising the imitation grout line. The protective section comprises at least a protective layer, and in some embodiments may comprise a clear polyvinyl chloride (PVC) material that is resistant to abrasion, and that is structured to avoid or reduce staining. In a preferred embodiment, the protective section additionally comprises a decorative layer disposed under the protective layer and made of a very thin, film-like material, such as PVC, and which further includes a colorant. In one or more of these embodiments of the invention, the exposed portion may be formed directly on the protective section, and more specifically, on the protective layer.

In at least one additional embodiment, the tile according to the present invention may further include a vinyl layer joined to the top section. The vinyl layer may also be joined to a core layer below, although a core layer is not strictly

6

required. In tiles comprising a vinyl layer, an exposed portion configured to imitate a grout line may be formed on at least a portion of the top section of the tile. In embodiments of the tile comprising a vinyl layer, the top section may comprise a first and a second wear layer, as well as a first and a second decorative layers. The first wear layer is generally coincident with the top surface of the tile. The first decorative layer is generally disposed below the first wear layer and is structured to imitate the feel of a natural material such as, but not limited to, naturally occurring stone or wood. The second wear layer is generally disposed below the first decorative layer and comprises a substantially equivalent structure to the first wear layer. The second decorative layer is generally disposed below the second wear layer and has a color that corresponds to an intended grout color. Generally, the exposed portion structured to imitate a grout line may be defined by exposing at least a portion of the second wear layer.

Additional features of the tile of the present invention include an interconnecting mechanism formed on at least one side of the tile to facilitate installation. For example, the interconnecting mechanism may comprise a “tongue” formed along one side of a tile, and a “groove” formed along one side of a different tile, and which are cooperatively structured to be matingly interconnected so as to join two different tiles together along their correspondingly disposed sides. Additionally, the “tongue” side and/or the “groove” side may each be configured to accommodate the exposed portion defining a gap along a side or edge of the tile. In one or more other embodiments, the inventive tile includes at least an extended interconnecting mechanism to facilitate installation of the tile on a vertical surface, such as a wall, as well as on other surfaces.

Other features of the tile of the present invention include a bevel comprising a slanted edge, formed on the side(s) of the tile, and specifically, adjacent to the exposed portion of the tile and textured surface. The sidewall associated with the exposed portion may include the bevel at an upper portion thereon, and in general, the bevel helps to more closely simulate the look and feel of a real grout line. The bevel may be formed in a variety of sizes, but in one embodiment, the angle of inclination of the bevel, with respect to the top surface of the tile, will be in a range between about 30° to about 90° although in an illustrated embodiment, this angle will be closer to about 12°. In general, in embodiments having a bevel, the intended width of the resulting simulated grout line will be a factor in determining the steepness of a corresponding angle of inclination. For example, a steeper angle of inclination may correspond to a grout line having a smaller width, while a less steep angle of inclination may correspond to a grout line having a larger width. Alternatively, the bevel may have a modified structure, such as a two staged descent from the top surface of the tile to the exposed portion and textured surface simulating a grout line. In another embodiment, the bevel may comprise a “micro” bevel.

In further embodiments of the present invention, for instance those wherein the top section of the tile merely comprises an enamel coating applied directly onto the core layer, with the enamel coating having at least one design element printed thereon, such a top section may further comprise a shielding layer. Such a shielding layer may be configured to, for instance, protect the tile from liquids, spills, abrasions, and deformations, and may be, in at least one embodiment, substantially transparent, such that the design feature(s) present on the enamel coating are visible. In at least one embodiment of the present invention, such a

shielding layer may comprise a topical coating, such as an acrylic solution, which may be applied through spray procedures or any other like process configured to apply a liquid coating onto the top surface of the tile. Alternatively, such a shielding layer may comprise a wear layer akin to the one previously discussed. Conversely, such a shielding layer may instead comprise a film layer, which itself may comprise a thin sheet of polypropylene, polyvinyl chloride, or some other material akin thereto, such as a thermoplastic polymer or a synthetic plastic polymer. As may be understood, alternative types, compositions, thickness, and material properties of such a shielding layer may vary dependent upon the intended application of the tile of the present invention. For instance, the use of the tile in residential, light contract, or heavy commercial applications may dictate the requisite properties of the shielding layer.

A primary object of the present invention is to provide a tile suitable for use as a flooring surface, which is made from synthetic materials and closely imitates the look of real stone, marble, ceramic or even wood flooring, but which also offers an imitation grout line with a highly realistic look and feel similar to that of an actual grout line.

Another primary object of the present invention is to provide an inventive tile made from synthetic material(s) that can be readily formed during the manufacturing process to define an exposed portion including a gap substantially or entirely along a selected side thereof and that can be readily profiled to achieve a texture surface thereon which closely matches the look and feel of an actual grout line.

Yet another primary object of the present invention is to provide a tile with a highly realistic looking and yet imitation grout line that can also be manufactured in variety of colors so as to offer a close match with and consistency of color relative to the overall color of the resulting tile, which has not been achieved before in any existing products.

An advantage of the tile of the present invention in at least some embodiments is that the material(s) used to make it is/are relatively lightweight and yet sufficiently rigid and durable for a wide variety of applications, and is/are also waterproof.

A feature of the tile of the present invention is that in at least some embodiments there is an interconnecting mechanism formed along at least one edge thereof or more that facilitates the assembly and installation process.

Another advantage of the tile of the present invention is that the materials(s) used to make it are capable of assuming a variety of different shapes, colors and/or designs.

These and other objects, features and advantages of the present invention will become clearer when the drawings as well as the detailed description are taken into consideration.

BRIEF DESCRIPTION OF THE DRAWINGS

For a fuller understanding of the nature of the present invention, reference should be had to the following detailed description, as taken in connection with the accompanying drawings, in which:

FIG. 1 is a transverse sectional view of a tile in accordance with the present invention comprising a top layer and a core layer, and illustrating an exposed portion formed in the top layer.

FIG. 2 is also a transverse sectional view of a tile in accordance with the present invention comprising a top layer and a core layer similar to FIG. 1, but illustrating the top layer as including both a polyvinyl chloride (PVC) layer and a wear layer.

FIG. 3 is also a transverse sectional view of a tile in accordance with the present invention comprising a top layer and a core layer similar to FIG. 1, but illustrating the top layer as including a polyvinyl chloride (PVC) layer, a decorative layer and a wear layer.

FIG. 4 is also a transverse sectional view of a tile in accordance with the present invention comprising a top layer and a core layer similar to FIG. 2, including the top layer having a polyvinyl chloride (PVC) layer and a wear layer, but illustrating the exposed portion formed on the core layer.

FIG. 5 is also a transverse sectional view of a tile in accordance with the present invention comprising a top layer and a core layer similar to FIG. 3, including the top layer having a polyvinyl chloride (PVC) layer, a decorative layer and a wear layer, but illustrating the exposed portion formed on the core layer.

FIG. 6 is also a transverse sectional view of a tile according to the present invention, but illustrating a preferred embodiment of the top layer and exposed portion, as well as a core layer and an interconnecting mechanism.

FIG. 7-A is also a transverse sectional view of a tile according to the present invention in another preferred embodiment comprising at least a top layer that includes a polyvinyl chloride (PVC) layer, and a core layer, and also an interconnecting mechanism, and illustrating an exposed portion having an imitation grout line formed in the PVC layer.

FIG. 7-B is also a transverse sectional view of a tile according to the present invention in yet another embodiment comprising at least a top layer, and a core layer, along with an interconnecting mechanism, and illustrating an exposed portion having an imitation grout line formed on the core layer.

FIG. 8 is a perspective view of the embodiment of the invention shown in FIG. 1 comprising a top layer and a core layer.

FIG. 9 is also a perspective view of the invention similar to FIG. 1 but illustrating another embodiment wherein the tile comprises a top layer including a wear layer, a decorative layer and a polyvinyl chloride (PVC) layer, as well as a core layer, and further, showing the exposed portion formed with most of the top layer removed so as to be disposed into the PVC layer.

FIG. 10 is also a perspective view of the invention similar to FIG. 1 but illustrating the embodiment wherein the tile comprises a top layer including a wear layer, a decorative layer and a polyvinyl chloride (PVC) layer, and further, showing the exposed portion having an imitation grout line formed on the core layer.

FIG. 11 is a perspective exploded view of the embodiment represented in FIG. 9.

FIG. 12 is a transverse sectional view of one embodiment according to the present invention having a bevel formed on the top layer.

FIG. 13 is a transverse sectional view of an alternative embodiment according to the present invention having a bevel formed on the core layer.

FIG. 14 is a transverse section view of yet another embodiment according to the present invention having a micro bevel formed on a top layer.

FIG. 15-A is a plan view of one preferred embodiment according to the present invention showing a tile comprising an exposed surface with an imitation grout line formed on all of its sides.

FIG. 15-B is a plan view of several tiles, each similar to the tile depicted in FIG. 15-A with an exposed portion and

imitation grout line formed on all of its sides, interconnected together to create a floor or wall covering.

FIG. 16-A is a plan view of another preferred embodiment according to the present invention showing a tile comprising an exposed surface with an imitation grout line formed on two of its sides.

FIG. 16-B is a plan view of several tiles, each similar to the tile depicted in FIG. 16-A with an exposed portion and imitation grout line formed on two of its sides, interconnected together to create a floor or wall covering.

FIG. 17-A is a plan view of another preferred embodiment according to the present invention showing a tile comprising an imitation grout line formed on two adjacent sides.

FIG. 17-B is a plan view of another preferred embodiment according to the present invention showing a plurality of interconnected tiles each comprising an imitation grout line formed on two adjacent sides.

FIG. 18 is a plan view of another embodiment of a tile according to the present invention, comprising an elongated interconnecting mechanism and an exposed portion structured to imitate a grout line.

FIG. 19 is a perspective view of another embodiment of a tile according to the present invention comprising a top section and a core layer and having an elongated interconnecting mechanism formed along one side thereof, and a mating interconnecting mechanism formed along an oppositely disposed side thereof.

FIG. 20 is a transverse sectional view of the embodiment of a tile shown in FIG. 19.

FIG. 21 is a transverse sectional view of another embodiment of a tile according to the present invention comprising a top section and a core layer, with interconnecting mechanism formed along opposite sides thereof, and including an exposed portion structured to imitate a grout line.

FIG. 22 is a transverse sectional view of a portion of two different tiles, each similar to that shown in FIG. 21, but illustrating the tiles matingly connected to each other.

FIG. 23 is a front view of two tiles, each similar to that shown in FIG. 21, illustrating a positioning of one tile relative to another in preparation for installation on surface.

FIG. 24 is a plan view of a plurality of tiles formed in accordance with one or more embodiments of the present invention, and illustrating the positioning and installation thereof on drywall surface, which itself is represented in a cutaway view.

FIG. 25 is a plan view of a plurality of tiles in another embodiment according to the present invention, wherein each tile comprises an additional exposed portion formed substantially across a middle section of the tile, as well as an exposed portions formed along one or more sides of the tile.

FIG. 26 is a transverse sectional view of another embodiment of a tile according to the present invention comprising a top section and a core layer.

FIG. 27 is a perspective view of the tile shown in FIG. 26.

FIG. 28 is a transverse sectional view of yet another embodiment of two tiles according to the present invention comprising a top section and a core layer.

FIG. 29 is a transverse sectional view of yet another embodiment of a tile according to the present invention comprising a protective section, a top section, and a core layer.

FIG. 30 is a transverse sectional view of one embodiment of a tile according to the present invention comprising a protective section with a protective layer and a decorative layer.

FIG. 31 is a transverse sectional view of another embodiment of a tile according to the present invention comprising a protective section with a protective layer and a decorative layer.

FIG. 32 is a transverse sectional view of one embodiment of a tile according to the present invention comprising a protective section, a top section, and a core layer, wherein an exposed portion is formed on a middle section of the tile.

FIG. 33A is a transverse sectional view of yet another embodiment of a tile according to the present invention comprising at least a vinyl layer and a top section, as well as an exposed portion formed in the top section, and a core layer which is optional.

FIG. 33B is a transverse sectional view of yet another embodiment of a tile according to the present invention having a vinyl layer, and a top section comprising a first and a second wear layer and a first and a second decorative layer.

FIG. 34 is a transverse sectional view of still another embodiment of a tile according to the present invention having a vinyl layer, and an exposed portion formed on at least a portion of a core layer.

FIG. 35A is a transverse sectional view of another embodiment of a tile according to the present invention comprising a vinyl layer, and an exposed portion formed substantially across a middle section of the tile.

FIG. 35B is a transverse sectional view of another embodiment of a tile according to the present invention comprising a vinyl layer, and an exposed portion formed on a second wear layer substantially across a middle section of the tile.

FIG. 36A is a transverse sectional view of one embodiment of a tile according to the present invention comprising a vinyl layer and a top section, as well as an exposed portion formed on the top section of the tile substantially above an interconnecting mechanism.

FIG. 36B is a transverse sectional view of another embodiment of a tile according to the present invention having a vinyl layer, and an exposed portion formed on a second wear layer of the top section of the tile substantially above an interconnecting mechanism comprising a male member.

FIG. 37 is a transverse sectional view of another embodiment of a tile according to the present invention having a vinyl layer, and an exposed portion formed on the top section of the tile substantially above an interconnecting mechanism comprising a female member.

FIG. 38 is a transverse sectional view of another embodiment of a tile according to the present invention comprising a vinyl layer, and an exposed portion formed on the top section of the tile substantially across a middle section of the tile.

FIG. 39 is a transverse sectional view of yet another embodiment of a tile according to the present invention comprising two vinyl layers, and an exposed portion formed on the top section of the tile.

FIG. 40 is a transverse sectional view of yet another embodiment of a tile according to the present invention comprising a top section and core layer having an exposed portion formed within such core layer.

FIG. 41 is a transverse sectional view of yet another embodiment of a tile according to the present invention comprising a top section and a core layer having an exposed portion formed within such core layer, such exposed portion having at least one protective coating disposed thereon.

FIG. 42 is a transverse sectional view of yet another embodiment of a tile according to the present invention comprising a top section, a core layer, and an exposed

11

portion, wherein such top section comprises an enamel coating having at least one design element imparted thereon, and further comprising a shielding layer.

FIG. 43 is a transverse sectional view of yet another embodiment of a tile according to the present invention comprising a top section and a core layer, wherein such top section comprises an enamel coating having at least one design element imparted thereon, such top section further comprising a shielding layer, wherein such tile comprises at least two exposed portions, wherein one such exposed portion is formed at a midpoint of the tile.

Like reference numerals refer to like parts throughout the several views of the drawings.

DETAILED DESCRIPTION

The present invention is directed towards a tile 1, such as a flooring tile, made from synthetic materials and so as to imitate the look and feel of real stone, marble, ceramic, wood or other materials, but which is further structured to offer a simulated grout line, with a highly realistic look and feel, on or along at least one side or edge of the tile 1. While the tile 1 of the present invention is particularly well suited for use as a flooring tile, it may also readily be used on wall surfaces or in a variety of other applications, and should not be considered as being limited only to flooring applications. As will also be described with regard to at least one embodiment, the tile 1 of the present invention may also be manufactured so as to include a very thin veneer layer of genuine wood or stone.

In general terms, the tile 1 of the present invention comprises an upper or top section, a lower or core section, and a plurality of sides. For example, and with reference to FIGS. 1 and 8, the upper or top section may be defined by a top layer 20, and the lower or core section may be defined by a core layer 30. As shown in FIG. 1, the top layer 20 comprises a first surface 22 that at least partially defines a top surface 10 of the tile 1, as well as a lower or second surface 24. The core layer 30 comprises an upper or third surface 32 adhered to or otherwise connected to the lower or second surface 24 of the top layer 20, so as to join the top layer 20 and core layer 30 together. The core layer 30 also comprises a fourth surface 34 that generally defines the bottom surface 12 of the tile 1, which will be adhered to an unfinished slab of concrete or other floor surface in a building. In some embodiments, however, the core layer 30 can include sublayers, such as a sound proofing or other material.

The tile 1 of the present invention may be formed in part from a vinyl material or a vinyl composite material, and may be referred to as a Vinyl Composite Tile (VCT). Although the top or upper section may be formed from a variety of materials, vinyl material(s) are preferred for a number of reasons, including the ability to offer a quality product at an affordable price point. The top layer 20 comprises a vinyl composite or a synthetic plastic polymer such as polyvinyl chloride (PVC). However, in at least one alternative embodiment, the tile of the present invention may include a top section comprised of a very thin layer of genuine wood or stone. As described more in detail herein, in most embodiments the top layer 20 will include a layer of polyvinyl chloride (PVC), such as a plasticized and/or extruded PVC, having a density that allows for a realistic looking grout line to be readily and consistently formed.

With reference now to FIGS. 2 through 7-B, and 9-11, in some embodiments the top layer 20 will comprise additional layers. For example, and as shown in FIGS. 2 and 4, the top

12

layer 20 is illustrated as comprising a wear layer 50 and a polyvinyl chloride (PVC) layer 40. In these and other embodiments, the wear layer 50 includes a top surface 52 which is entirely or at least partially coincident with the top surface 10 of the tile. The wear layer 50 may vary in thickness according to its intended use such as residential, light contract, heavy commercial or other type of use. The wear layer 50 will preferably be formed during the manufacturing process so as to include one or more design features, such as a texture with some undulation to imitate the look and feel of real stone or marble or a texture that has grooves and/or other impressions to imitate the look and feel of, for example, a real piece of wood. In the embodiments shown in FIGS. 2 and 4, the polyvinyl chloride (PVC) layer 40, such as extruded PVC, is generally disposed between the wear layer 50 and the core layer 30. For example, the polyvinyl chloride (PVC) layer 40 may be connected at its upper surface 42 by way of adhesives and/or pressing to a lower surface 54 of the wear layer 50, and similarly connected at its lower surface 44 to an upper surface 32 of the core layer 30. The polyvinyl chloride (PVC) layer 40 may comprise a material of synthetic plastic polymer such as polyvinyl chloride (PVC) or may be made out of or so as to include other materials. However, since it includes polyvinyl chloride (PVC) it will be referred to herein throughout as the polyvinyl chloride (PVC) layer 40. In the preferred embodiments the polyvinyl chloride (PVC) layer 40 has a density in a range of between generally about 2,000 kg/m³ (124.856 lb/ft³) to about 2,400 kg/m³ (149.827 lb/ft³). In at least one embodiment, the density of the polyvinyl chloride (PVC) layer 40 is generally about 2,000 kg/m³ (124.856 lb/ft³). In at least one or more additional embodiments, however, the polyvinyl chloride (PVC) layer comprises another density which can be anywhere in a range from generally about 1,600 kg/m³ (about 99.884 lb/ft³) up to generally about 2,600 kg/m³ (about 162.313 lb/ft³).

With reference now to FIGS. 3, 5, 6, 7-A and 7-B, and FIGS. 9-11, the top layer 20 of the inventive tile 1 may comprise a wear layer 50, a polyvinyl chloride (PVC) layer 40 and also a decorative layer 60. The decorative layer 60 may comprise a film or sheet that may be made from a variety of materials such as, but not limited to, polyvinyl chloride (PVC). The decorative layer 60 will also preferably comprise one or more design features that help to provide an authentic look of a selected material, such as real stone, real marble, ceramic, wood, or another surface. For example, the decorative layer 60 may comprise a film having decorative features corresponding to the look and coloring of a natural wood grain or a wood flooring plank. In the embodiments of FIGS. 3, 5 through 7B, and 9-11, the decorative layer 60 is disposed in interconnecting relation between the wear layer 50 and the polyvinyl chloride (PVC) layer 40. These layers may be adhesively connected or interconnected by a variety of adhesives known in the art, such as but not limited to glue. For example, and as can be appreciated from FIGS. 9 and 11, the decorative layer 60 includes an upper surface 62 connected to the lower surface 54 of the wear layer 50, and also, a lower surface 64 connected to the upper surface 42 of the polyvinyl chloride (PVC) layer 40. Additionally, the wear layer 50 may be made so as to have a substantially translucent or transparent appearance. When the wear layer 50 is made of a translucent or transparent material, it permits the design features carried on the decorative layer 60 to be readily seen there-through. In one or more embodiments, a coating of another material may be applied to the top surface 10 of the wear layer 50. By way of example, this coating may comprise a ethoxyline resin (ER) or a polyurethane

(PU) material, which may be cured using an ultra-violet (UV) lighting and heating process. It is within the scope of this invention, however, to provide a tile **1** with or without the decorative layer **60**.

Additionally, it is within the scope of the present invention to provide a tile **1** that comprises waterproofing properties. As such, the materials of the different layers of the top layer **20** as well as of the core layer **30**, may all comprise waterproofing properties. Similarly, adhesives used to connect these layers may also have waterproof properties.

As mentioned previously, the material composition of the top layer **20** may vary, but in at least one embodiment, the top layer **20** generally comprises a mixture of polyvinyl chloride (PVC), as well as calcium powder, oil, and a foaming agent. In one preferred embodiment, the material composition of the top layer **20** may be about 20% to about 30% polyvinyl chloride (PVC), about 60% to about 70% calcium powder, about 5% to about 10% oil, and about 0.5% to about 5% foaming agent.

The tile **1** of the present invention also includes a lower or core portion, which may be defined by a core layer **30** as shown in FIGS. 1-14. The core layer **30** is preferably formed from a material to allow the tile **1** to be rigid as well as waterproof. In the preferred embodiments, the core layer **30** comprises a densified foam material, and further, will preferably be relatively light weight. In some cases, the core layer comprising a densified foam material may be referred to as a Wood Plastic Composite (WPC), but the composition of the core layer should not be construed as being limited to this. Additionally, the core layer **30** may have a smooth texture. In some embodiments, the tile **1** may comprise one or more sublayers joined to the core layer **30** to serve as an underlayment or to attenuate sound. These sublayers may be made of other materials such as laminate foil, cork, foam, or ethyl vinyl acetate.

While the material composition of the core layer **30** may vary, it comprises in at least one embodiment a combination of a synthetic plastic polymer such as polyvinyl chloride (PVC), calcium powder, and a foaming agent. In a preferred embodiment, the densified foam material of core layer **30** comprises polyvinyl chloride (PVC) in an amount of generally between about 50% to about 55%, calcium powder in an amount of generally between about 40% to about 45%, and foaming agent in an amount of generally between about 5% to about 10%. The foaming agent may be a mixture of materials that enhance stability. In another preferred embodiment, the densified foam material of core layer **30** comprises a foam sheet formed from polyvinyl chloride (PVC) in an amount of generally between about 45% to about 50%, calcium powder in an amount of generally between about 45% to about 50%, and foaming agent in an amount of generally between about 5% to about 10%. In yet another preferred embodiment, the densified foam material of core layer **30** comprises a foam sheet formed from polyvinyl chloride (PVC) in an amount of generally about 46.5%, calcium powder in an amount of generally about 46.5%, and foaming agent in an amount of generally about 7%.

Also in certain preferred embodiments of the tile **1**, the core layer **30** comprising a densified foam material will have a density within an optimal range from about 800 kg/m³ (which is about 49.942 lb/ft³) to about 900 kg/m³ (which is about 56.185 lb/ft³), which aids in ensuring that the tile **1** is sufficiently rigid and durable for flooring applications. In another preferred embodiment, which is helpful to flooring applications, the density of the core layer **30** is between about 850 kg/m³ (which is about 53.064 lb/ft³) to about 900

kg/m³ (which is about 56.185 lb/ft³). It should be appreciated that while this is considered an optimal range, the density of the core layer **30** can also vary outside of this range, and still be within the spirit and scope of the present invention.

For example, in one or more alternative embodiments of the inventive tile **1**, the core layer **30** may comprise a different density, such as within a range from about 500 kg/m³ (about 31.214 lb/ft³) to about 2,000 kg/m³ (about 124.856 lb/ft³). In at least one or more additional embodiments, the core layer **30** may comprise a different density in a range anywhere from generally about 500 kg/m³ (about 31.214 lb/ft³) up to generally about 1,500 kg/m³ (about 93.642 lb/ft³).

As a specific but non-limiting example, and with reference to FIGS. 18-24, the inventive tile **1** can also be readily used as a wall panel, with several such wall panels being used to cover a wall surface. Since wall panel(s) will not be subject to a load from foot traffic or from the weight of heavy items such as furniture, etc., the inventive tile **1** may have core layer **30** with a lower density in a different optimal range of about 500 kg/m³ (about 31.214 lb/ft³) to about 900 kg/m³ (about 56.185 lb/ft³). As will be described in more detail subsequently herein, with regard to wall installations, the inventive tile **1** having a core layer **30** within this lower density range is advantageous as it provides for a relatively flexible tile **1** that facilitates installation, particularly when a connector is used, or when a number of connectors are used, to attach the tile to a surface, such as a wall.

As another example, however, in one or more alternative embodiments of the inventive tile **1**, the core layer **30** may comprise a different density, such as within a range from about 1,200 kg/m³ (about 74.914 lb/ft³) to about 2,000 kg/m³ (about 124.856 lb/ft³).

As yet another specific and non-limiting example, and with reference to FIGS. 26-28, the inventive tile **1** can include a core layer **230** formed of a stone plastic composite (SPC) material which, if used primarily to cover a floor surface, will be subject to heavier loads from foot traffic, the weight of furniture and the like. Therefore, the core layer **230** in such alternative and other embodiments intended for flooring applications may have a higher density, as will be described in more detail subsequently herein.

In general, the overall thickness of the tile **1** may range from about 4 millimeters to about 12 millimeters (which is from about 0.157 inches to about 0.472 inches), depending on the particular embodiment. In one or more embodiments of the tile **1**, the overall thickness of the tile **1** from the top surface **10** of the top layer **20** to the bottom surface **34** of the core layer **30** will preferably be generally about 7 millimeters (about 0.275 inches), with the core layer **30** having a thickness in a range of generally between 4 millimeters to about 6 millimeters (about 0.016 inches to about 0.236 inches). In embodiments of the tile **1** wherein the top layer **20** includes a wear layer **50** and a polyvinyl chloride (PVC) layer **40**, the top layer **20** may comprise a thickness of about 1.5 millimeters (about 0.059 inches) to about 2 millimeters (0.079 inches). For example, the wear layer **50** between its top surface **52** and lower surface **54** may be in a range of between generally about 0.3 millimeters (about 0.012 inches) to about 0.7 millimeters (about 0.028 inches). Also, the thickness of the polyvinyl chloride (PVC) layer **40** between its top surface **42** and lower surface **44** may be in a range of between generally about 1.0 millimeters (about 0.039 inches) to about 1.5 millimeters (about 0.059 inches), or even to about 2.0 millimeters (0.079 inches).

15

In embodiments of the tile **1** including a decorative layer **60**, such as shown in FIGS. **3**, **5** through **7-B**, and **9-11**, the thickness of the decorative layer **60** between its top surface **62** and bottom surface **64** may be in a range of generally about 0.05 millimeters (about 0.002 inches) to about 0.1 millimeters (about 0.004 inches). As illustrated in FIG. **6**, the core layer **30** may comprise a thickness of about 5 millimeters (about 0.197 inches), with the top layer **20** comprising a thickness of generally about 2 millimeters (about 0.079 inches), including a wear layer **50** having a thickness of about 0.5 millimeters (about 0.02 inches), a polyvinyl chloride (PVC) layer **40** having a thickness of about 1.43 millimeters (about 0.056 inches), and a decorative layer **60** having a thickness of about 0.07 millimeters (about 0.003 inches). As mentioned above, the thickness of the tile **1** may range from about 4 millimeters (about 0.016 inches) to about 12 millimeters (about 0.472 inches).

However, and in other embodiments, the inventive tile **1** may have a different overall thickness and still be within the intended spirit and scope of the present invention. Some non-limiting examples of such alternative embodiments will be described with reference to FIGS. **26** through **28**.

In one alternative embodiment, however, and as best shown in FIGS. **4-5**, and **7-B**, the inventive tile **1** may comprise a polyvinyl chloride layer **40** having a substantially reduced thickness between its top surface **42** and lower surface **44**. For example, the thickness of the polyvinyl chloride (PVC) layer **40** may be approximately 0.3 millimeters (about 0.012 inches), which as described subsequently herein, may facilitate exposing at least a portion of the core layer **30** as the exposed portion **18** during the manufacturing process. In such embodiments, the overall thickness of the tile **1** will be generally about 5 millimeters (about 0.197 inches) to about 6.5 millimeters (about 0.256 inches), and preferably, approximately 5.9 millimeters (about 0.232 inches).

As noted above, the tile **1** of the present invention additionally comprises a plurality of sides, such as **16** or **16'**, and may also come in different shapes and in varying dimensions. For example, and as shown in the illustrative embodiments of FIGS. **8-11** and **15-A** to **17-B**, the tile **1** of the present invention may have a substantially rectangular shape with four sides **16** or **16'**. The dimensions of such a tile **1** having a rectangular shape may be, by example only, twelve (12") inches by twenty-four (24") inches, but can readily be varied to other appealing dimensions, and may even assume a much longer length so as to be a wall plank or floor plank of, for example, twelve (12") inches by forty-eight (48") inches, which can be cut into individual panels. As another example, the tile **1** of the present invention might have a square shape. Moreover, the tile **1** of the present invention might also have six or eight sides **16** or **16'** as is the case with tiles having hexagonal or octagonal shapes. Other shapes, including those comprising an uneven number of sides, are also possible depending on the overall desired visual effect.

The tile **1** of the present invention also includes along at least one of its sides, such as **16**, an exposed portion **18**. As illustrated in FIGS. **1-14**, this exposed portion **18** extends outwardly below and away from the top surface **10** of the tile **1**, and is defined in part by a sidewall **15** formed within at least said top layer **20**. As will be described subsequently herein, the exposed portion **18** effectively defines a gap **14** in the plane of the top surface **10** of the tile **1** that, as perhaps best shown in FIGS. **8-14**, preferably extends uniformly and either completely or substantially along the length of the side **16**. In at least one embodiment, such as is illustrated in

16

FIG. **6**, this exposed portion **18** is configured to be located at a depth of generally about 0.9 millimeters (about 0.035 inches) from a top surface **10** of the tile, or in a range from about 0.9 millimeters (about 0.035 inches) up to about 2 millimeters (about 0.079 inches) from the top surface **10** of the tile **1**. This exposed portion **18** also includes a textured surface structured to closely represent the look and feel of an actual grout line. As will also be described subsequently herein with reference to FIGS. **15-A** through **17-B**, when a plurality of the inventive tiles **1** are assembled and installed with their exposed portions **18** disposed in an operative orientation, they will collectively offer to a person standing close by or a few feet away (or more) a highly realistic appearance both in terms of the tile's similarity itself to a selected material such as real marble, stone, or ceramic, but importantly, also **1** in terms of the tiles **1** having the appearance of an actual grout line caused in large part by the depth of the exposed portion **18** and the width of the gap **14** relative to the top surface **10** of the tile **1**, as well as the textured surface of the exposed portion **18**. Moreover, the top layer **20** and/or core layer **30** may be manufactured to include a dye that may match or be representative a variety of grout colors so as to correspond with the intended coloring of the overall tile **1**.

As is also shown in FIGS. **1-14**, the exposed portion **18** of the tile **1**, including the sidewall **15** associated therewith, can be seen to effectively define a gap **14**. The width **W** of the exposed portion **18**, and the gap **14** created thereby, will in the preferred embodiments be substantially uniform along a length of the side **14** of the tile, and may range from being nearly imperceptible, but still visible, to a width **W** of about 6 millimeters (about 0.236 inches), or more, depending on the desired look of the overall surface. The embodiment of FIG. **6**, however, illustrates an exposed portion **18** having a width **W** of approximately 5 millimeters (about 0.197 inches). Additionally, the embodiment of FIG. **6** illustrates a sidewall **15** that extends into the polyvinyl chloride (PVC) layer **40** of the top layer **20**, so that the exposed portion **18** is formed on or within the PVC layer **40** at a depth **D** of generally about 0.9 millimeters (about 0.035 inches) below the top surface **10** of the tile. However, the exposed portion **18** may be located at another depth, but preferably within a range of between generally about 0.9 millimeters (about 0.0354 inches) to about 2 millimeters (about 0.079 inches) from the top surface **10** of the tile **1**. This range should **1** be considered an approximation as during the production of the tile(s) **1**, variations, such as within 0.1 millimeters (about 0.004 inches), are likely, which may enhance the realistic appearance of the imitation grout line of the tile(s) **1**.

The aforesaid exposed portion **18** having a textured surface structured to represent the look and feel of an actual grout line is ideally achieved during the manufacturing process for the inventive tile **1**. More specifically, in the process of manufacturing the tile **1**, a tool such as a press and/or router or another instrument, such a cutting blade(s), a profiling knife, etc. may be applied to the tile **1**, such as to the top layer **20**, along at least one side or edge **16**. The press and/or router or other tool may be used to remove all or substantially all of the top layer **20** extending along a selected side **16** of the tile **1**, so as to expose a portion of the polyvinyl chloride (PVC) layer **40** and define the exposed portion **18** in outwardly extending relation to a selected side, such as **16**, of the tile **1**. In the preferred embodiments, the density of the polyvinyl chloride (PVC) layer **40** should be between generally about 2,000 kg/m³ (which is about 124.856 lb/ft³) to about 2,400 kg/m³ (which is about 149.827 lb/ft³), in order to permit the tool, cutting blade(s),

knife or other instrument to cut into and profile the polyvinyl chloride (PVC) layer 40 to form the sidewall 15 and exposed portion 18, and to create a texture surface thereon that ideally approximates that of fine sand. Additionally, this density range provides sufficient structural integrity to the polyvinyl chloride 1 (PVC) layer 40 so that it does not disintegrate, rupture, tear or otherwise incur damage during the cutting and profiling process. In an alternative embodiment, during the process of manufacturing the tile 1, the tool or instrument used may remove more of the top layer 20 extending along a selected side 16 of the tile, so as to expose a deeper profile into at least a portion of the core layer 30 as well.

Also, in the preferred embodiments of the tile 1 as shown in FIGS. 2-3, 6, 9, and 11-14, the exposed portion 18 is formed on the polyvinyl chloride (PVC) layer 40. As will become clear from the discussion below, during the manufacturing process, when a portion of the top surface 10 of the tile 1 is removed along one side, such as 16 thereof, preferably at a depth of between 0.9 millimeters (about 0.035 inches) to 2 millimeters (about 0.079 inches) below the plane of top surface 10, at least a portion of the polyvinyl chloride (PVC) layer 40 will be exposed and formed to define the exposed portion 18, including a sidewall 15 and a gap 14. Alternatively, and as has been described relative to FIGS. 4, 5 and 7-B, the thickness of the polyvinyl chloride (PVC) layer 40 may be substantially reduced so as to facilitate exposing at least a portion of the core layer 30 to define the exposed portion 18 and gap 14 thereon.

In another embodiment of the inventive tile 1, the top layer 20 may comprise yet a further additional layer for reasons which will now be described. More specifically, and in those embodiments wherein the top layer 20 includes a polyvinyl chloride 1 (PVC) layer 40 having a dye or colorant(s) and a decorative layer 60, an additional layer, which may be in the form of a coating, may be connected to and disposed between the polyvinyl chloride (PVC) layer 40 and the decorative layer 60. This additional layer may comprise a thin layer of raw polyvinyl chloride (PVC) material which is typically black in color, but in at least one other embodiment this additional layer may comprise a coating of material having a tonality that approximates a black color. The need in some embodiments for an additional layer arises because the decorative layer 60 is generally designed to be used with or against a dark background such that it can adequately reflect the desired tones of a selected color and/or overall designs appearing on the decorative layer 60. Therefore, some embodiments of the inventive tile 1 may comprise yet an additional layer of PVC or a black coating applied to the polyvinyl chloride (PVC) layer 40 to serve as a dark background for the decorative layer 60, which preferably has a tonality that approximates a black color or other dark background colors such as, but not limited to dark brown or dark grey. Also, the need for some embodiments of the tile 1 to include this additional layer or coating arises because during the formation of the polyvinyl chloride layer 40, when the raw polyvinyl chloride (PVC) is mixed with a dye or colorant(s), higher concentrations of the dye or colorant may accumulate towards the bottom and top surfaces of the PVC layer 40.

Accordingly, to help ensure that the color of the imitation grout line 1 being formed on the tile 1 on or as part of the polyvinyl chloride (PVC) layer 40 is substantially uniform, in the preferred embodiments no more than approximately 0.4 millimeters (about 0.016 inches) of material should be removed from the polyvinyl chloride (PVC) layer 40 itself, so as to create the exposed surface 18 at a desirable depth

within the PVC layer where the dye or colorant(s) tend to accumulate. In at least one preferred embodiment, the depth of the material removed to create the exposed surface 18 in the PVC layer 40 will be less and generally only about 0.33 millimeters (about 0.013 inches) of material should be removed. In other words, because the dye or colorant(s) tend to accumulate at the upper and lower surfaces of the PVC layer 40, an optimal depth in some embodiments at which the exposed portion 18 will be disposed or located will be generally between approximately 0.33 millimeters (about 0.013 inches) to approximately 0.4 millimeters (about 0.016 inches) below the top or fifth surface 52 of the polyvinyl chloride (PVC) layer 40. This ensures that the exposed portion(s) 18 is formed on sections of the polyvinyl chloride (PVC) layer 40 that comprise an adequate or otherwise sufficient amount of dye or colorant.

With reference now to FIGS. 6, 7-A and 7-B, the inventive tile 1 may additionally comprise an interconnecting mechanism formed on the sides 16 or 16' of the tile 1. For example, the interconnecting mechanism of the present invention may comprise a "tongue" side 70 formed on or along one side 16 of the tile 1, and a "groove" side 80 formed on or along a different side 16' of a different tile 1. The "tongue" side 70 and the "groove" side 80 are configured so as to be joined together in mating engagement and facilitate both the installation and alignment of the tiles 1 during installation. Additionally, either the "tongue" side 70 and/or the "groove" side 80 may be formed on the tile 1 primarily as part of the core layer 30 as shown in FIGS. 6-7-B. The "tongue" side 70 and the "groove" side 80 may also be structured so as to permit slight movement and/or rotation between two adjacent tiles, which permits adjustment of one tile relative to another to accommodate uneven substrates, or a slab of concrete that is not perfectly level, as is often the case with unfinished floors and/or walls. As such, either the "tongue" side 70 or the "groove" side 80 may be formed at least partially within the top layer 20 as shown in FIGS. 6-7-A.

With reference now to FIG. 6, in a preferred embodiment the inventive tile 1 will have an exposed portion 18 formed on a side 16 thereof which corresponds to the "tongue" side 70 only, and not to the "groove" side 80. In the embodiment of FIG. 6, the gap 14 defined by exposed portion 18 and sidewall 15 is also partially defined by the top layer 20 and edge 16' of an adjacent tile 1 which includes the "groove" side 80. Alternatively, as is shown in the embodiments of FIGS. 7-A and 7-B, the "tongue" side 70 and the "groove" side 80 of the tile 1 may each be configured to include an exposed portion 18 having the textured surface that imitates the grout line. Other embodiments are also within the scope of the present invention wherein the exposed portion 18 may be formed on a tile 1 with a "groove" side 80, and not on the "tongue" side 70. Moreover, the tile 1 of the present invention may be cooperatively configured with different mechanical joining systems made by a variety of manufacturers. These mechanical joining systems may include a relatively new "click-lock" type of mechanical joining system used during installation of a variety of surfaces such as imitation flooring tiles.

With reference now FIGS. 18-24, in certain embodiments the inventive tile 1 can also be structured to facilitate installation, particularly on a vertical wall surface, but also on other surfaces including if desired, a ceiling.

For example, and with initial reference to FIG. 18, the inventive tile 1 in such embodiments may be provided with an elongated interconnecting mechanism 125 on or along at least one side thereof 16. The elongated interconnecting mechanism 125 is structured and disposed to receive a

19

portion of one connector there-through such as at **130**, or a plurality of connectors, to attach the tile **1** to an underlying surface, such as an unfinished drywall surface, and ideally in a manner that conceals the connector in the finished installation. Additionally, and with reference to FIGS. **19** and **20**, in embodiments of the tile **1** having the elongated interconnecting mechanism **125**, the tile **1** will preferably also include, but does not have to include, a mating interconnecting mechanism **115** formed on or along an oppositely disposed side **116** thereof, for reasons which will become clear from the description subsequently herein, below.

Additionally, the inventive tile **1** having an elongated interconnecting mechanism **125** will, in most embodiments but not necessarily in all embodiments, include an exposed portion **18** structured to imitate the look and feel of a real grout line. As has been described previously herein, the exposed portion **18** which provides a realistic looking grout line may be formed along at least one side of the tile **1**, such as at **116**, as shown in FIGS. **18** and **21**. In such embodiments, the exposed portion **18** may be formed in a top section of the tile **1**, such as a polyvinyl chloride (PVC) layer **40** in the manner described previously herein. Alternatively, and with reference to the embodiments of FIGS. **19** and **20**, the inventive tile **1** having an elongated interconnecting mechanism **125** may also be provided without an exposed portion(s) **18**.

In other embodiments, the inventive tile **1** having an elongated interconnecting mechanism **125** may also comprise one or more sub-layers that serve as an underlayment or sublayer such as for sound attenuation. Such sublayer(s), may be made from materials suitable for this purpose, including but not limited to cork, laminate foil, a thin layer of foam, or ethyl vinyl acetate (EVA), and may be connected to or otherwise adhesively joined to a bottom surface of the core layer **30** of the tile **1**.

Referring now to FIGS. **19** and **20**, in one embodiment the inventive tile **1** includes an elongated interconnecting mechanism **125** that comprises a lower extended segment **120** formed on at least part of one side **16** of the tile **1**. Preferably, however, the elongated interconnecting mechanism is formed along substantially all, and ideally along all of the side **16** of the tile **1**, and further, so as to have a substantially uniform configuration. As shown in FIGS. **19** and **20**, the lower extended segment **120** extends outwardly and beyond an upper edge **22'** associated with the top surface **10** of the tile **1**. As perhaps best illustrated in FIG. **20**, the lower extended segment **120** itself may comprise a top portion **122** and a bottom portion **124** and, while the particular configuration of the lower extended segment **120** may vary, it will preferably extend outwardly from and coplanar with the top surface of the tile **1** at a distance **D** of generally about 11 millimeters (about 0.433 inches). While this distance **D** can also vary, it will preferably be in a range of between about 8 millimeters (about 0.315 inches) to generally 13 millimeters (about 0.512 inches). Also, this distance **D**, which may be considered the width dimension of the lower extended segment **120**, is sized, dimensioned and configured to provide sufficient space or physical room for receiving a one or more connectors, disposed in an operative position on or along the length of side **16** of the tile **1**, used during installation to secure the tile **1** to an underlying surface or substrate, such as a wall or a ceiling.

Additionally, in the illustrated embodiment of FIGS. **19** and **20**, the lower extended segment **120** is formed on or from the core layer **30** of the tile **1**. For example, during manufacture of the tile **1**, the lower extended segment **120** may be formed by removing sufficient material from the

20

layer(s) of the tile **1** above the core layer **30**, such as the top section **20** of the tile **1**, which as described previously herein may have one or more layers, to reveal the top portion **122** of the lower extended segment **120** and to define the lower extended segment **120** at a desirable distance below the upper edge **22'** associated with the top surface of the tile **1**. As an alternative, one or more layer(s) of the tile's **1** top section **20** may be disposed in an offset relation to the core layer **30**, to define the lower extended segment **120**, as illustrated in FIG. **21**. It should be appreciated that in other embodiments, however, the lower extended segment **120** could alternatively be formed on a polyvinyl chloride (PVC) layer **40** of the tile **1** associated with the top section **20**, rather than being formed on the core layer **30**.

As also shown in the illustrated embodiment of FIGS. **19** and **20**, the lower extended segment **120** may comprise a lateral portion **126**, in addition to a top portion **122** and a bottom portion **124**. As such, an overlapping portion **128** is also formed on the tile **1** in this illustrated embodiment, and defines a lip extending along the side **16** of the tile **1** that serves to partially define the lower extended segment **120** as a channel that also extends along the side **16** of the tile **1**. As will become clear from the description subsequently herein, this embodiment having the lower extended segment **120** comprised of a channel facilitates installation of the tile **1** and further, operates to reduce or eliminate shifting or displacement of the tile **1**, following installation of the tile **1** on a vertical surface such as a wall in particular. In the illustrated embodiment of FIGS. **19** and **20**, as well as in FIG. **21**, the overlapping portion **128** is formed by or within the top section **20** of the tile, and as also shown, is disposed in an offset relation relative to the core layer **30** of the tile **1**, from which the bottom portion **124** and lateral portion **126** of the lower extending segment **120** are formed. Also in the illustrated embodiment of FIGS. **19** and **20**, the width of the overlapping portion **128** will preferably be about 3 millimeters (about 0.118 inches), but in other embodiments could be quite small at about 1 millimeter (about 0.039 inches) or alternatively, larger to a width of about 5 millimeter (about 0.197 inches). In addition, the height of the lateral portion **126** may be in a range from anywhere of about 1.5 millimeters (0.059 inches) to about 2.0 millimeters (0.079 inches). It should be appreciated that these dimensions are approximated for the illustrated embodiment, and can be varied while still yielding a tile that is within the spirit and scope of the invention.

As also shown in FIGS. **18** and **19**, the intended location of a connector on the elongated interconnecting mechanism **125** is indicated in phantom lines at **130**. In this embodiment, three connector locations **130** are illustrated on the lower extended segment **120** of the tile **1** although it should be appreciated that the number of connectors can be more depending on the length of the particular tile **1**, or in some cases, less. The type of connector received on the lower extended segment **120** of the tile **1** can also vary, and may include flat-head screws, bolts, "Tapcon" concrete screws, or other types of screws, fasteners, and the like. One of these connectors may be drilled, screwed, or otherwise driven directly into one of the intended locations **130** on the lower extended segment **120** of the tile **1**, and into the underlying substrate. By way of example, in drywall applications, installation of the tile **1** will typically involve at least two connectors, such as two flat-head screws, to secure the tile **1**, which will preferably occur at the location of a support stud for the drywall or closely adjacent thereto. An additional connector may be installed on the tile **1** and fastened to the drywall that is not at an approximate location of a

21

drywall stud. It is worth pointing out that if such flat-head screws are used to secure the tile **1** to a drywall surface, they will ideally be driven through the lower extended segment **120** and into the underlying surface behind the tile **1**, so that the flat-head portion thereof is substantially aligned or flush with the top portion **122** of the lower extended segment **120**. For various reasons, it is preferable that the head of the connector be in such substantial alignment, including so as to only minimally interfere with, if at all, the movement of the upper extended segment **110** into sliding engagement with the lower extended segment **120**.

Additionally, and as previously mentioned herein, the inventive tile **1** may have a core layer **30** formed to have an optimal density in a lower range than other embodiments disclosed herein. As an example, when the inventive tile **1** is used as wall panel, the core layer **30** may have a density in a range from about 500 kg/m³ (about 31.214 lb/ft³) to about 900 kg/m³ (about 56.185 lb/ft³). By providing the inventive tile **1** with a core layer **30** having a lower density, it results in a rigid, yet lighter, softer and somewhat more flexible tile **1**, compared to other embodiments disclosed herein having higher density ranges for the core layer **30**. This is advantageous, particularly for use on wall surfaces, because a lighter tile **1** is less likely to cause bowing of or to otherwise distort the underlying surface. Additionally, when the inventive tile **1** is being applied to a wall, there should be no load from foot traffic, furniture, etc., and consequently a higher density and level of rigidity associated therewith is not strictly needed. Moreover, when the inventive tile **1** comprises an elongated interconnecting mechanism for use with a connector, the lower density of the core layer **30** more readily receives the connector(s) without incurring damage. Conversely, a tile **1** with a higher density of the core layer **30** is likely to be more susceptible to damage when a connector is installed through the core layer **30**.

In one alternative embodiment of the present invention, a tile(s) **1** may be provided with pre-drilled holes at the intended locations **130** of the connector(s). The predrilled holed may even be, if desired, dimensioned to correspond to the size of the connector(s).

Still referring to FIGS. **19** and **20**, and as noted previously herein, the tile **1** including an elongated interconnecting mechanism **125** along one side **16**, will preferably also include a mating interconnecting mechanism **115** formed on and ideally along an oppositely disposed side **116** thereof, or also an adjacent side, which will also have a substantially uniform configuration. In the illustrated embodiment of FIGS. **19** and **20**, the mating interconnecting mechanism **115** comprises an upper extended segment **110** having a top portion **112** and a bottom portion **114**. However, the bottom portion **114** is illustrated as having a width dimension **W** that is larger or wider than that of the top portion **112**. As a non-limiting example, the bottom portion **114** of the upper extended segment **110** may have a width dimension **W** that is generally about 13 millimeters, although this could be anywhere in a range from about 10 millimeters to about 15 millimeters. In contrast, the top portion **112** may comprise a much smaller width dimension of about 3 millimeters (about 0.118 inches), although this could be anywhere in a range from about only 1 millimeter (about 0.039 inches) to about 5 millimeters (about 0.197 inches). It should again be appreciated that these dimensions are approximated for the illustrated embodiment, and can be varied while still yielding a tile that is within the spirit and scope of the invention.

With reference now to FIG. **22**, a pair of tiles **1A** and **1B** are illustrated in an embodiment according to the present invention, and shown in an assembled state, with the edges

22

16 and **116** of the tiles matingly joined together. More specifically, the elongated interconnecting mechanism **125** on a first tile **1A** is illustrated as being joined to the mating interconnecting mechanism **115** on a second tile **1B**. As represented in FIG. **22**, when these two tiles **1A** and **1B** are connected, the lower extended segment **120** faces and/or abuttingly engages with the upper extended segment **110**. Additionally, a distal section of the upper extended segment **110** of the tile **1B** is matingly received within the channel defined by the overlapping portion **128** and the lower extended segment **120** on the adjacent tile **1A**. As stated previously herein, this mating interconnection is operative to reduce or eliminate shifting or displacement of the tile **1B** during and after installation.

Still referring to FIG. **22**, the illustrated embodiment of tile **1B** is shown to include a mating interconnecting mechanism **115** that is structured and disposed to be slidably inserted into the elongated interconnecting mechanism **125** of tile **1A**. More specifically, the upper extended segment **110** of mating interconnecting mechanism **115** is formed to be slidably moved on the lower extended segment **120** of tile **1A** into a position, as shown, with its distal end inserted into the channel defined by the overlapping portion **128**, top portion **122** and lateral portion **126** thereof. Accordingly, the bottom portion **114** of the upper extended segment **110** is structured so as to be capable of sliding with respect to the top portion **122** of the lower extended segment **120**, such that, and as represented in FIG. **22**, when the two tiles **1A** and **1B** are connected, the top portion **122** of the lower extended segment **120** of tile **1A** faces and abuttingly engages the bottom portion **114** of the upper extended segment **110** of tile **1B**. In the illustrated embodiment, and as shown in FIG. **20**, this is accomplished by the upper extended segment **110** having a width dimension **W** that is slightly larger than the dimension **D** of the lower extended segment **120**.

Consequently, and in the illustrated embodiment shown in FIG. **22**, a recess, indicated as **140**, may be formed in the space between the edges **16** and **116** of the joined tiles **1B** and **1A**. More specifically, the recess **140** may comprise a small gap formed between the proximal end **118** of the upper extended segment **120** on tile **1B**, and the outer lower edge **16'** of the adjacent tile **1A** corresponding to the lower extended segment **120**. The recess **140** facilitates installation of tile **1B** relative to tile **1A** and also allows for dimensional adjustments between them after installation. That is, even after the upper extended segment **110** of tile **1B** has been inserted into the elongated interconnecting mechanism **125** of tile **1A**, the recess **140** allows for some micro dimensional adjustments during installation, such as by allowing the upper extended segment **110** to slide slightly relative to the lower extended segment **120**. It is pointed out, however, that while a recess **140** has been described and illustrated herein for achieving the slidable insertion of one tile, such as **1B** having a mating interconnecting mechanism **115** into another tile, such as **1A** having an elongated interconnecting mechanism **125**, it would also be within the spirit and scope of the present invention to utilize other structures for achieving this purpose, or even to reverse the configuration of the structures described herein.

As briefly described above, the illustrated embodiment in FIG. **22** which depicts two tiles **1A** and **1B**, each having a mating interconnecting mechanism **115** and an elongated interconnecting mechanism **125**, allows for an easy and efficient installation of a plurality of such tiles onto a surface such as a wall, as is generally reflected in FIGS. **23** and **24**. More specifically, a tile such as **1A** may be positioned first

23

on a wall surface in a desired location with the elongated interconnecting mechanism **125** exposed. To assist with ascertaining a desired location for the tile **1A**, guide lines may be pre-marked on the wall or other surface to indicate the intended location(s) where the tiles **1A**, **1B**, and/or the sides **16'** thereof should be aligned, as shown at **160** in FIG. **24**. Once a desired location is determined, the first tile **1A** may be positioned on the wall surface and oriented with the elongated interconnecting mechanism **125** disposed in an upwardly facing orientation, as shown in FIG. **23**. The lateral side(s) **16'** of the tile **1A** may be substantially aligned with a structure on the wall surface, whether a corner, a door, a window, etc., such as shown at an initial position **170** in FIG. **24**. One or more connectors can then be drilled into the exposed lower extended segment **120** at locations such as **130**, shown in at least FIGS. **18-19** and **23-24**, to attach the tile **1A** to the wall surface. The connector(s) are ideally driven far enough through the lower extended segment **120** and into the wall surface so that the head portion of the connector is in close alignment with the lower extended segment **120**, and the top portion **122** thereof in particular.

Thereafter, a second tile, such as **1B** may then be relatively easily assembled into place adjacent the first tile **1A**, with the mating interconnecting mechanism **115** generally aligned with the elongated interconnecting mechanism **125**, and then slidably moved into mating engagement in the direction of arrow **Y** shown in FIG. **23**. As has been described previously herein, the mating engagement between tiles **1A** and **1B** may be defined by the upper extended segment **110** on tile **1B** being slidably moved on the lower extended segment **120** of tile **1A** and into position with its distal end inserted into the channel defined by the overlapping portion **128**, top portion **122** and lateral portion **126** thereof, as shown in FIG. **22**. In the preferred embodiments, once tile **1B** has been positioned to be matingly joined with tile **1A**, the elongated interconnecting mechanism **125** associated with tile **1B** on an opposite edge thereof, will be now be exposed, also ideally in an upwardly facing orientation, as best shown in FIG. **23**. Consequently, one or more connectors can then be drilled into the exposed lower extended segment **120** of tile **1B**, as described, followed by the introduction of a third tile having the mating interconnecting mechanism **115** formed thereon for being matingly joined with the elongated interconnecting mechanism **125** of tile **1B**. This process may be repeated as many times as needed to complete an installation of the tiles **1** on a surface.

Additionally, once a plurality of tiles such as **1A** and **1B** in FIG. **23** have been assembled and installed, the upper extended segment **110** of a tile **1B** serves to conceal the one or more connectors, as well as the lower extended segment **120** through which they pass, to attach the tile to the wall or other surface.

As an alternative, one or more tiles **1** according to the present invention may be glued directly onto the underlying surface, whether a wall, floor, ceiling, etc.

With reference now to FIG. **21**, the illustrated embodiment of the tile **1** additionally includes an exposed portion **18** that closely imitates the look and feel of a real grout line. As shown, the exposed portion **18** is formed on a side **116** of the tile **1** corresponding to the mating interconnecting mechanism, and upper extended segment **110** so that the imitation but realistic looking grout line will still be visible in the final installation.

With reference now to FIG. **24**, a plurality of the inventive tiles **1** described herein are shown, each as having a substantially rectangular configuration, and in an offset pattern

24

or "staggered" relationship to one another. For example, in FIG. **24**, three tiles, marked as **1**, **2**, and **5**, each comprise a substantially equivalent length, whereas tiles marked as **3** and **4** may comprise a different, reduced length and/or may be cut or otherwise modified during the installation process. One or more connectors may be installed at intended locations **130** on the lower extended segment of the tile **1**, some of which should be in alignment with the location **150'** of a supporting drywall stud **150**, with the approximate locations **150'** of the supporting drywall studs **150** being represented with broken lines. Once the first tile **1** is secured in an initial position, such as **170** in FIG. **24**, a second tile **2** may be inserted or slid into a side **16'** of the first tile **1**. Subsequently, further connectors may be installed on the tile **2** at intended locations **130** on the lower extended segment thereof **120** to secure it to the drywall. Thereafter, another tile **4** may be positioned on top of tile **1** and its upper extended segment **110** slidably inserted into the lower extended segment of tile **1**, to begin creating a second row **180** of tiles. As also shown in FIG. **24**, a tile **4** may be inserted into tile **1**, and tile **5** may be inserted into a portion of tile **1** and into a portion of tile **2** to create a substantially offset pattern. Additional rows of tiles **1** may be installed above to substantially cover the intended surface. Installation does not necessarily have to be done from right to left, as it may also be done from left to right.

The production process for the inventive tile **1** can vary, but generally comprises different production sequences. For example, the core layer **30** may be produced by mixing together the raw materials, such as a PVC material, calcium powder and foaming agent, and any accessory materials, and applying heat to melt the mixture. The melted materials may be then placed into an extrusion machine that molds the melted material into boards. At this stage, foaming material may be added to facilitate production and thereafter, a resting or curing stage for roughly 24 to 36 hours. The production process for the top layer **20** also comprises mixing together the raw materials, such as a PVC material, calcium powder, oil and a foaming agent, and any accessory materials, and applying heat to the mixture to melt it. Then the melted materials may be pressed over one or more pressing stages to form vinyl pieces, which at this point, are likely to include a textured surface. Thereafter, the vinyl pieces, which essentially form the top layer **20**, may be pressed with a decorative layer **60**, such as a thin film sheet of polyvinyl chloride (PVC). A UV coating may later be added to the top surface **10**.

After production of the top layer **20** and the core layer **30**, individual sheets of both may be adhesively joined or glued together to form the desired tile(s) **1** as shown for example, in FIGS. **8-11**. After application of the glue or other adhesive(s), the assembled layers are pressed, for example, by a cold pressure machine in a thermostatic chamber for about 6 hours to about 8 hours. After pressing, the assembled layers may be left in the thermostatic chamber for about 36 hours to about 48 hours to rest or cure. Thereafter, the assembled layers or master-boards may be cut into smaller sizes. The master-boards generally have a dimension of about 2 meters to about 3 meters, but may have different dimensions. After the assembled layers or master-boards are cut into smaller sizes, each individual piece may be passed through a machine that gives one or more sides **16** or **16'** of a tile an individual profile. This profile may include forming modifying, roughening or otherwise cutting the sides **16** or **16'** of the assembled tiles **1**. At this stage, either or both of the exposed surface **18**, having the imitation grout line, or

25

the interconnecting mechanism may be formed. Thereafter, the tile(s) 1 may be packaged for shipment.

As previously mentioned, the tile 1 of the present invention can be configured to imitate the feel or texture of a real material such as real stone, marble, ceramic, wood, or another material. Accordingly, during the pressing stage a customized texture may be given to the wear layer 50 of the tiles 1. A computer may be used to configure a press according to a decorative design, such as a visual design of the decorative layer 60, so that the press gives the wear layer 50 a corresponding texture. More specifically, a picture of the intended decorative design may be inputted into a computer so as to program the press accordingly.

For use as a flooring application, a plurality of the inventive tiles 1 will be disposed next to each other in an operative orientation. As such, a side of one tile 1 will be disposed next to the side of a different tile 1. As mentioned previously, the exposed portion 18 of the inventive tile 1, and the gap 14 defined thereby, may have varying dimensions. Also, and with reference now to FIG. 15-A, in one embodiment of the tile 1 having a rectangular configuration, each of the four sides 16 may have an exposed portion 18 and a textured surface formed thereon. In such an embodiment, the exposed portion 18 and textured surface formed on each side 16 may be sized to equal generally one half ($\frac{1}{2}$) of the overall, intended resulting size of the imitation grout line formed between tiles, as illustrated in FIG. 15-B. For example, the width of the exposed portion 18 and textured surface may be generally about 2.5 millimeters (about 0.098 inches) to about 3 millimeters (about 0.118 inches). As such, an entire simulated grout line comprising the exposed portion 18 and texture surface thereon may be formed between two adjacent tiles and have a width of generally about or between 5 millimeters (about 0.197 inches) and 6 millimeters (about 0.236 inches).

In an alternative embodiment, and with reference now to FIGS. 16-A and 17-A, an inventive tile 1 may have an exposed portion 18 and textured surface formed on only two sides 16 thereof, each of which is sized to equal generally all or substantially all of the grout line formed between tiles. That is, and as shown in FIGS. 16-A and 17-A, a tile 1 may have two sides 16 that each include an exposed portion 18 and a textured surface formed thereon, and two sides 16 that do not. For example, and as is perhaps best shown in FIG. 16-B, each side(s) 16 of the tile 1 having an exposed portion 18 may be disposed next to a side 16' of a tile 1 that does not have such structure. In this embodiment, the exposed portion 18 and textured surface may be sized to have a width of generally about or between 5 millimeters (about 0.197 inches) to 6 millimeters (about 0.236 inches). When two or more of such tiles 1 shown in FIG. 16-A or 17-A are disposed next to each other, as shown in FIGS. 16-B and 17-B respectively, the visual effect that results is a full imitation grout line formed around all sides of each tile. However, other combinations of the size and location of the exposed portion 18 are also possible.

With reference now to FIG. 25, an additional feature of the present invention comprises forming the exposed portion 18 at a middle or central section 28 of the tile 1, in addition to, or instead of, one of its side(s) 16. More specifically, it is often desirable to provide a surface, such as a wall or a floor surface, with a visual appearance of several tiles 1 being disposed in an even arrangement, wherein the four corners of four different but adjacently disposed tiles meet at a common point, as can be appreciated by the arrangement of tiles in FIG. 25. From an installation and durability perspective, there are disadvantages associated with the

26

even arrangement of tiles as this common point is often weak and makes the tiles 1 susceptible to damage. The present invention addresses this disadvantage by providing a substantially rectangular tile 1 that imitates the appearance of two different substantially square tiles 1, and in some embodiments more than two square tiles.

More specifically, and as shown in FIG. 25, each one of tiles labeled as TILE 1, TILE 2, TILE 3, TILE 4 and TILE 5 has a substantially rectangular shape, with a length that is approximately twice their individual width, such as a length of 24 inches by a width of 12 inches. Furthermore, each one of these TILES 1-5 preferably comprises an exposed portion 18 formed along one or more its sides 16 to closely imitate the look and feel of a real grout line, as described previously herein. However, the inventive tiles shown in FIG. 25 each includes another exposed portion, namely, a middle exposed portion, indicated as 18' formed substantially across a middle portion 28 of the tile's visible top surface 10, which is also structured to closely imitate the look and feel of a real grout line, as described previously herein. As illustrated, the middle exposed portion 18' is disposed within a middle or central portion 28 of the TILE 1, and may extend completely across the top surface 10 thereof between opposite side(s) 16 of the TILE 1. For purposes of clarity, the middle exposed portion 18' may be formed on the tile 1 in the in a manner similar to embodiments previously described herein, such as being formed in the polyvinyl chloride (PVC) layer 40 at a depth below the top surface 22 of the tile 1. In other embodiments, the middle exposed portion 18' may be formed in the core layer 30.

However, and as illustrated in FIG. 25, when a plurality of such substantially rectangular tiles, such as those labeled TILE 1, TILE 2, TILE 3, TILE 4 and TILE 5, are installed next to each other in an offset manner, so as to form a "staggered arrangement" similar to that shown in FIG. 24, the resulting appearance will be that of an even arrangement or several squares as shown in FIG. 25. For illustrative purposes, each one of the substantially rectangular TILES 1-5 has a first portion labeled as "A," and a second portion labeled as "B," such as "1A" and "1B" in TILE 1, "2A" and "2B" in TILE 2, etc. Each portion, "A" and "B" of each TILE 1-5 is intended to create the visual impression of being one individual tile having a substantially square shape. Said differently, each substantially rectangular TILE 1-5 is intended to provide a visual appearance of two substantially square tiles. A staggered arrangement may thus be created by disposing the portion "B" of one tile next to the portion "A" of a different tile. This may be done in a "horizontal" manner, such as disposing portion "2A" right next to portion "1B". This may also be done in a "vertical" manner such as disposing portion "3A" directly below portion "1B", and portion "4A" below portion 5B". This arrangement may be repeated so that the exposed portion 18 of one side(s) 16 of a tile offering a realistic looking grout line is disposed in alignment with the middle exposed portion 18' of a different tile, which also includes a realistic looking grout line.

For example, and still referring to FIG. 25, the exposed portion 18 of the left side 16 of TILE 3, namely, that marked with tile portion "3A," may be disposed in alignment with the middle exposed portion 18' of TILE 1, and more specifically, with the middle exposed portion 18' formed across TILE 1 between portions "1A" and "1B". Also by way of example, the exposed portion 18 formed on the right side 16 of TILE 3, namely, that marked with tile portion "3B," may be disposed in alignment with the exposed portion 18 formed on the left side 16 of TILE 4, namely, that marked as "4A," such that both of these exposed portions 18 are

disposed in substantially parallel alignment with each other, and also in alignment with the middle exposed portions **18'** of TILE **2** immediately above, namely, that marked between "2A" and "2B", and also in alignment with the exposed portion **18'** of TILE **5** immediately below, namely, that marked between "5A" and "5B".

As may be appreciated from FIG. **25**, the visual result offered by the offset or staggered arrangement of the substantially rectangular TILES **1** through **5**, each of which has the middle exposed portion **18'** formed thereon, is a substantially even arrangement appearing to be several square tiles arranged with a common point between the four corners of four different but adjacently disposed tiles. The actual physical arrangement formed by TILES **1** through **5**, however, while achieving this visual result, includes an actual common point between only two corners of two different but adjacently disposed tiles. As a result, the weakness associated with the common points, where four different corners of four different tiles are adjacent to each other, is minimized, and the chance of tiles being damaged at such common points is greatly reduced.

Moreover, this benefit offered by the present invention can be significantly increased. Specifically, while the size of the substantially rectangular tiles shown in FIG. **25** are likely to be offered in a common rectangular shape of 12 inches in width by 24 inches in length, this can be increased to a much larger size, such as 12 inches by 48 inches in length, with each such larger tile formed to have additional middle exposed portions **18'** across the middle and other sections thereof, so that when arranged with other such tiles in an offset or staggered arrangement, the visual result will still offer an appearance of evenly arranged tiles, similar to several aligned square tiles forming a grid. However, the common points between four actual corners of four adjacently disposed tiles will be minimized. It should be appreciated, of course, that other dimensions and/or configurations of the inventive tile shown in FIG. **25** are also within the scope of the present invention.

With reference back now to FIGS. **12-14**, the tile **1** of the present invention may also comprise a bevel **90** formed on one or more side(s) **16** of the tile **1** adjacent to the exposed portion **18** and gap **14**. The bevel **90** may be formed on the sidewall **15** associated with the exposed portion **18**, at an upper portion thereof so as to be formed on the top layer **20**, and specifically on the wear layer **50**. The bevel **90** comprises a slanted portion that slopes downwardly, away from the top surface **10** of the tile **1** and towards the sidewall **15** that at least partially defining the exposed portion **18**. Preferably, the bevel **90** is formed to extend uniformly and coincident with sidewall **15**, exposed portion **18** and gap **14** along all or substantially all of one the side(s) **16** of the tile **1**. Additionally, the bevel **90** may comprise a variety of sizes and angles of inclination with respect to the top surface **10** of the tile **1**. For example, the bevel may have an angle of inclination that can range from generally about thirty degrees (30°) to about ninety degrees (90°). The illustrative embodiment of FIG. **12** shows a bevel **90** having an angle of inclination of generally thirty degrees (30°). In an alternative embodiment shown in FIG. **13**, the bevel **90** may instead comprise a two stage descent from the top surface **10** to the sidewall **15** defining exposed portion **18** and gap **14** of the tile **1**. With reference to FIG. **14**, the bevel **90** may alternatively comprise a "micro" bevel **90'**. As another example, and as shown in FIG. **13**, the bevel **90** may additionally be formed on the exposed portion **18** itself, and may correspond with either the core layer **30** and/or the polyvinyl chloride (PVC) **40** layer instead of the top layer **20**. In such cases, the

bevel **90** may have a slanted portion with an angle of inclination of generally about ten degrees (10°).

With reference now to FIGS. **26-28**, yet additional features of the present invention can include providing a tile **200** with a core layer **230** comprised of a material different from previous embodiments described herein. For example, the inventive tile **200** may also be formed so as to include a material such as stone plastic composite (SPC), which may also be referred to at times as a stone polymer composite (SPC). Stone plastic composite (SPC) is generally a mixture of materials that includes densified foam polyvinyl chloride (PVC) and stone dust, or an equivalent material, and will typically be about two times the weight (or more) of the core layer **30** described previously herein as a densified foam material, and is also sometimes referred to as "rigid board." Such alternative embodiments using SPC material to form the core layer **230** are likely to prove advantageous because the properties of an SPC material include being more resistant to expansion and/or contraction. More specifically, the expansion coefficient of a stone plastic composite (SPC) is lower than that of other materials used in flooring applications, and therefore, stone plastic composite (SPC) material reduces the possibility that the overall tile **200** will flex, bend, or otherwise expand in ambient conditions. Using a stone plastic composite (SPC) material may also result in reduced or no dimensional shifting that might otherwise occur between individual tile(s) **200** after installation.

Accordingly, and in one or more additional embodiments, the core layer **230** of the present inventive tile **200** comprises a stone plastic composite (SPC) material structured to provide additional rigidity and sufficient support for a top section **220** of the inventive tile **200**, so that the resulting tile **200** is especially suitable for flooring applications. For example, in one or more of such embodiments, the core layer **230** comprises a stone plastic composite (SPC) material having an optimal density in a preferred range from anywhere of about 1,500 kg/m³ (about 93.642 lb/ft³) to about 2,000 kg/m³ (about 124.856 lb/ft³). In at least one preferred embodiment, however, the core layer **230** comprising a stone plastic composite (SPC) material will have a density that is generally between 1,900 kg/m³ (about 118.613 lb/ft³) to about 2,000 kg/m³ (about 124.856 lb/ft³). Additionally, in one or more embodiments, such as shown in FIG. **27**, the top section **220** of the tile **200** may comprise a polyvinyl chloride (PVC) layer **240**, although as described subsequently herein, given the properties of a core layer **230** that includes SPC, this is not necessary and a top section **220** formed of different materials is also possible.

Indeed, and as previously stated, the top section **220** may comprise a veneer layer or layer of other material, including a coating of material, which may be referred to as (but not limited to) an enamel coating **521**. This coating of material may comprise an acrylic and/or a polycrylic coating that is initially in liquid form and applied directly onto the core layer **530** via spraying procedures or other similar processes. Such an enamel coating may be comprised of a colored appearance, or may be clear, and may be applied through spraying processes or other means similarly situated to apply a topical liquid enamel coating directly onto the core layer **230**. This coating of material may comprise an acrylic and/or polycrylic coating, a polyurethane coating, and/or an ethoxylene resin which may be configured to seal any cracks or gaps inherent in the core layer due to the chemical composition thereof. More specifically, because the core layer of at least one embodiment of the present invention may have a naturally porosity associated therewith, such an enamel coating may be configured as a fill coating in order to seep

29

into such porous surface and create a smooth surface upon which design element(s) may be printed.

For instance, as previously stated, such an enamel coating may be configured for the application of at least one design element thereon. Such at least one design element may itself comprise, for instance, texture, grooves, impressions, undulations, color or graphical designs, or any other feature now known or hereafter developed. In at least one embodiment of the present invention, such design element(s) may be configured to imitate the texture and appearance of a real materials, such as genuine stone, marble, or wood. However, other appearances of such design element are envisioned herein. Such at least one design element may be applied onto the enamel coating of the top section 220 of the tile of at least one embodiment of the present invention via, for instance, printing processes. As shown in FIG. 28, in one or more embodiments, the top section 220 of the tile 200 may comprise a wear layer 250 and a decorative layer 260. A lower surface 254 of the wear layer 250 may be joined to a top surface 262 of the decorative layer 260. A top surface 252 of the wear layer 250 may be substantially coincident with the top surface of the tile 200. Thus, in FIG. 28 the top section 220 comprises a wear layer 250 and a decorative layer 260, but not a polyvinyl chloride (PVC) layer 240, joined directly to the core layer 230. More specifically, a lower surface 264 of the decorative layer 260 may be joined directly to the core layer 230 comprising a stone plastic composite (SPC) material. The wear layer 250 and/or the decorative layer 260 may comprise a relatively thin film or sheet formed from polyvinyl chloride (PVC), although it is possible that other materials may be utilized. In embodiments wherein the tile 200 includes both a core layer 230 comprising stone plastic composite (SPC) material and a polyvinyl chloride (PVC) layer 240, the density of the core layer 230 will preferably be greater than the density of the PVC layer 240.

In one or more of the embodiments wherein tile 200 has a core layer 230 comprising a stone plastic composite (SPC) material and a wear layer 250, the thickness of the wear layer 250 may be in a range from about 0.1 millimeters (about 0.004 inches) to about 0.7 millimeters (about 0.028 millimeters), and in some embodiments a thickness of about 0.3 millimeters (0.012 inches) to about 0.5 millimeters (0.020 inches). Additionally, a polyurethane (PU) coating may be applied to one or more layers to at least partially reduce scratching of a layer(s) below.

Additionally, in one or more embodiments wherein the core layer 230 comprises a stone plastic composite (SPC) material, the thickness of the tile 200 or portions thereof may be reduced. For example, the core layer 230 may have a thickness in a range from anywhere of about 3 millimeters (about 0.118 inches) to about 8 millimeters (about 0.315 inches), which together with the density of the core layer 230, is likely to reduce the chances that the tile 200 will crack due to heavy foot traffic. In one preferred embodiment, the thickness of the core layer 230 will be reduced to approximately 4 millimeters (about 0.157 inches). As an additional non-limiting example, the overall thickness of the tile 200 having a core layer 230 comprised at least in part of stone plastic composite (SPC) and including a top section 220 may be about 5 millimeters (about 0.197 inches). As yet another non-limiting example, when a tile 200 having a core layer 230 comprised at least in part of stone plastic composite (SPC) includes a top section 220 including a PVC layer 240, the latter may have a thickness of about 1 millimeter (0.039 inches) to about 2 millimeters (0.079 inches).

30

Also, there can be other embodiments wherein the inventive tile 200 comprises a core layer 230 that is at least partially made from a stone plastic composite (SPC) material, and wherein the top section 220 is manufactured so as not to include a polyvinyl chloride (PVC) layer 240. For example, in one embodiment, a tile 200 according to the present invention may be provided with a core layer 230 comprising a stone plastic composite (SPC) material, and a relatively thin veneer layer 220. The veneer layer 220, which may comprise a "raw" veneer formed from a variety of materials, will preferably comprise one or more layers of natural stone or of genuine wood. In such embodiments, the thickness of the veneer layer 220 may now be produced to be very thin, such as within a range from anywhere of about 0.3 millimeters (about 0.012 inches) to about 1 millimeter (about 0.039 inches). In one preferred embodiment, the thickness of the veneer layer 220 is about 0.6 millimeters (about 0.024 inches) as in initial testing for durability, favorable results have been observed. In at least one embodiment, a liquid vinyl compound may be applied to the veneer layer 220 for additional wear and/or moisture resistance. As previously stated, such a veneer layer 220 may instead comprise another material or even a coating of material, which may be referred to but is not limited to an enamel coating, such as a fill coat or some other acrylic and/or polyacrylic coating applied directly onto the core layer. Likewise, as previously stated, at least one embodiment of the present invention may further comprise the application of a shielding layer onto the veneer layer 220 and/or enamel coating. Accordingly, it may be understood such a shielding layer may comprise the aforementioned liquid vinyl compound applied onto the veneer layer 220 for wear and/or moisture resistance.

With regard to the material composition of the core layer 230 comprising a stone plastic composite (SPC) material, while there may be various formulations, in at least one embodiment this comprises a combination of stone dust, a synthetic plastic polymer such as polyvinyl chloride (PVC), calcium powder, and a chemical agent. In a preferred embodiment, the stone plastic composite (SPC) material of the core layer 230 comprises polyvinyl chloride (PVC) in an amount of generally between about 20% to about 30%, calcium powder or stone dust in an amount of generally between about 70% to about 80%, and a chemical agent, in an amount of generally between about 0.5% to about 5%. In at least one embodiment the chemical agent may be provided in an amount of about 0.5% to about 2%. The chemical agent may include a lubricating agent, a bonding agent, and/or a stabilizer. In yet another preferred embodiment, the stone plastic composite (SPC) material of the core layer 30 comprises polyvinyl chloride (PVC) in an amount of generally about 24.8%, calcium powder in an amount of generally about 74.5%, and a chemical agent in an amount of generally about 0.7%. The core layer 230 may be formed as an extruded sheet.

With reference now to FIGS. 29-32, in one or more additional embodiments of the present invention, tile 300 is configured to reduce or avoid staining of the exposed portion(s) 18 and/or 18' comprising the imitation grout line, whether from dirt, oils, dropped food, spilled liquids, etc. For example, the tile 300 shown in FIG. 29 includes a protective section 370 disposed between a top section 320 and a core layer 330, and with the exposed portion 18 formed within the protective section 370.

Still referring to FIGS. 29-32, the top section 320 of the tile 300 has a top surface 310, which can be configured to imitate the look and feel of natural materials, as described

31

previously herein, such as natural stone, genuine wood, etc. For example, and as shown in FIGS. 30 and 31, the top section 320 of the tile 300 may comprise a wear layer 350 and/or a first decorative layer 360 structured to imitate the look of a desired natural material. The material of the wear layer 350 may be made so as to have a substantially translucent or transparent appearance to permit the design features of the first decorative layer 360 to be seen there-through. The wear layer 350 may comprise a clear polyvinylchloride (PVC) material, and further, may be formed with nano-crystals, e.g., made of micro-ceramic beads or aluminum oxide crystals, so as to be resistant to abrasion. Additionally, the tile 300 illustrated in these embodiments comprises a core layer 330 made of a densified foam material, as previously described herein. In some cases, the core layer comprising a densified foam material may be referred to as a Wood Plastic Composite (WPC), but should not be construed as being limited to this. In other embodiments, it is possible for the core layer 330 to comprise a stone plastic composite (SPC) material, as has also been described herein

As best shown in FIG. 30, in one or more embodiments the top section 320 of the tile 300 additionally comprises a layer of a polyvinyl chloride (PVC) material 340. The polyvinyl chloride layer (PVC) 340 may comprise natural or otherwise "virgin" polyvinyl chloride (PVC). This layer of PVC material 340 is preferably disposed between the first decorative layer 360 of the top section and the core layer 330, and is structured to enhance the rigidity and stability of the tile 300, particularly in those embodiments where the core layer 330 comprises a densified foam material.

As shown in FIGS. 29-31, the inventive tile 300 also comprises at least one exposed portion 18 formed on at least one its sides 16, which is structured to represent an imitation but highly realistic looking grout line. In these embodiments, the exposed portion(s) 18 and/or 18' is formed directly on or within the protective section 370.

The protective section 370 comprises at least a protective layer 380 in one embodiment, but in the preferred embodiments, comprises both a protective layer 380 and another or second decorative layer 390, as shown in FIGS. 30 through 32. In these embodiments, the protective layer 380 is disposed above and/or in immediately adjacent, covering relation to the second decorative layer 390. Also in these embodiments, the protective layer 380 preferably comprises a material that is either transparent or substantially translucent, so as to permit one or more design features associated with the second decorative layer 390 to be observable therethrough, such as a coloring thereof, that will generally be an intended color of the exposed portion 18 or 18' which closely simulates a real grout line. Ideally, the material of the protective layer 380 is clear or at least translucent, so that the design features of the second decorative layer 390 can be observed, and with little to no distortion. The second decorative layer 390 may comprise a very thin film having a solid color. However, this is not strictly required as it is possible that the second decorative layer 390 comprises a relatively thin film with other design features and/or patterns. Additionally, the protective layer 380 is preferably formed from a vinyl composite material, including a synthetic plastic polymer which may be, but is not limited to, polyvinyl chloride (PVC). During the manufacturing process for the tile 300, the exposed portion 18 can be formed by a cutting process utilizing a knife, cutting blade(s), etc. to remove material from the top section 320 and side(s) 16 of the tile 300, to reveal the protective layer 380, and to form the exposed portion(s) 18 and/or 18' within the protective layer 380 and with a size, shape and texture that closely imitates

32

the look and feel of a real grout line. Accordingly, the vinyl composite material of the protective layer 380 is sufficiently rigid and structured to not only permit the formation of the exposed portion 18, but to withstand wear and tear conditions associated with flooring, whether from being walked upon, furniture being moved, etc. In addition, the protective layer 380 is structured to provide protection to the exposed portion(s) 18 and/or 18', comprising the imitation grout line, so as to avoid or limit any staining thereof, whether from dust, grease, dirt, oils, pieces of food or other particles.

In one or more embodiments, such as but not limited to one where the core layer 330 comprises a stone plastic composite (SPC) material, a coating of another material may be applied to the top surface of the protective layer 380. By way of example only, this coating may comprise an ethoxylated resin (ER) or a polyurethane (PU) material, which may be cured using an ultra-violet (UV) lighting and heating process. Further, such a coating may comprise an ultra-violet (UV) cured polyurethane (PU) material that may additionally comprise nano-silica, ceramic beads, or otherwise aluminum oxide crystals. Such a coating may be applied during the manufacturing process before boards are cut into individual planks or tile sizes. For most embodiments described herein, however, a tile 300 having a protective section 370 will not need a further protective coating or painting applied to the exposed portion 18 having the appearance of grout line after the tile 300 is manufactured.

With reference now to FIGS. 30-31, the thickness of the different sections 320, 370 and 330, as well as the various layers of material within them, may vary according to the intended or particular application. As a non-limiting example, the top section 320 of tile 300 may have a depth or thickness in a range of generally about 1.27 millimeters to about 2.77 millimeters (about 0.05 inches to 0.109 inches), comprising a wear layer 350 with a thickness in a range from about 0.2 millimeters (0.008 inches) to about 0.7 millimeters (0.028 inches), a first decorative layer 360 with a thickness of about 0.07 millimeters (about 0.003 inches), and a polyvinyl chloride layer (PVC) 340 having a thickness in a range of about 1 millimeter (about 0.039 inches) to about 2 millimeters (0.079 inches). The protective section 370 may have a depth or thickness in a range of generally about 0.11 millimeters to about 0.69 millimeters (0.004 inches to 0.027 inches), comprising a protective layer 380 with a thickness in a range from about 0.1 millimeter (about 0.004 inches) to about 0.6 millimeters (0.024 inches) and a second decorative layer 390 of about 0.01 millimeters (about 0.0004 inches) to about 0.09 millimeters (about 0.0035 inches). In at least one preferred embodiment, however, the thickness of the protective layer 380 is about 0.3 millimeters (about 0.012 inches) and the thickness of the second decorative layer 390 is about 0.07 millimeters (about 0.0028 inches). Further, the core layer 330 may have a depth or thickness in a range from about 3 millimeters (about 0.118 inches) to about 6 millimeters (about 0.236 inches). As has been described previously herein, the depth of the exposed portion 18 and/or 18', from the top surface 310 of the tile 300, can vary, such as for example, within a range between about 0.9 millimeters to 2 millimeters. However, in some embodiments, the depth of the exposed portion 18 and/or 18' from the top surface 310 may be less, whether from a slight or minimal depth that may be about 0.3 millimeters deep, or at a greater depth such as up to about 1 millimeter (about 0.039 inches). It is emphasized that the foregoing is provided only for illustrative purposes and should not be construed in a limiting sense.

With reference now to FIG. 32, another feature of the tile 300 having a protective section 370 is to achieve a substantially uniform appearance, at least in the color of a plurality of exposed portions 18 and/or 18' formed thereon. For example, a tile 300 having an exposed portion 18 structured to represent a grout line formed along one side thereof as shown in FIG. 30, may further include additional exposed portion(s) 18' representing a grout line that is formed substantially at or across the top surface 310, such as but not limited to, across a central or middle section of the tile 300, as shown in FIG. 32 and indicated by the dashed lines at 28. A tile 300 having a protective section 370, as described herein, is structured to provide a substantially uniform color and appearance to these different exposed portions 18 and/or 18' irrespective of their location on the tile 300 and how each is formed during the manufacturing process. For example, the exposed portion(s) 18 are typically formed along the side(s) 16 of a tile 100 during manufacture using a cutting process with one or more blades applied horizontally, e.g., by a saw or other machine, in generally parallel relation to the tile 1. Conversely, to form the exposed portion(s) 18' across a middle section 28 of a tile as shown in FIG. 32, the cutting process uses one or more blades applied vertically or in perpendicular relation to the tile 300.

By providing tile 300 with a protective section 370, and forming the exposed portions 18 and/or 18' within protective layer 380, substantially uniformity can be achieved for a plurality of different exposed portion(s) 18 and/or 18' in terms of the coloring thereof corresponding to imitation grout lines, as the protective layer 380 provides even distribution for the colorant or dye. In contrast, when an exposed portion(s) 18 or 18' is formed directly on a core layer, or on a polyvinyl chloride layer, it is difficult to ensure a consistent appearance and color of the exposed portions 18 and/or 18' because during the manufacturing process, any colorant or dye added to the core layer 330 or polyvinyl chloride (PVC) layer 340 tends to accumulate on the sides, or at the top or bottom surfaces, rather than being evenly distributed, so that when the various exposed portions 18 and/or 18' are formed, the color of the imitation grout line may be less than consistent. Moreover, the protective layer 380 of tile 300 allows for the texture of various exposed portions 18 and/or 18' to be highly similar in appearance, despite some inconsistencies in how the cutting process is applied.

With reference now to FIGS. 33A-39, the tile of the present invention is also capable of yet further embodiments. More specifically, the inventive tile 400 can comprise at least a top section 420 and a vinyl layer 470, as well as an exposed portion(s) 18 structured to look like and closely imitate a real grout line, and further along with a core layer 430 in certain embodiments, although this core layer 430 is not always required.

Also, and as with other embodiments described herein, the tile 400 may be configured so that the top surface 410 imitates the look and feel of natural materials, including, but not limited to, natural stone, genuine wood, etc. For example, as shown in FIGS. 33B, 34, 35B and 36B, the top section 410 of the tile 400 may comprise a first wear layer 450 and/or a first decorative layer 460 structured to imitate the look of a desired material.

However, and as is also shown in FIGS. 33B, 34, 35B and 36B, the inventive tile 400 includes a top section 410 comprising a second wear layer 440 and/or a second decorative layer 490. The second decorative layer 490 is structured to include a color that will preferably correspond to an intended grout color. Additionally, the material of the second

wear layer 440 is preferably structured to at least partially reduce staining, and generally provides protection to the second decorative layer 490 below. The wear layer(s) 450 and/or 440 may comprise a substantially translucent material so that the design features of the decorative layer(s) 460 and/or 490 may be seen there-through.

As represented in FIGS. 33A-35B and 39, the inventive tile 400 may further comprise a core layer 430. The core layer 430 is adhered to or otherwise joined to the vinyl layer 470 and may comprise a rigid material, such as a stone plastic composite (SPC) material, or alternatively, a densified foam material, as previously described herein.

However, and as represented in FIGS. 36A-38, it is also within the scope of the present invention to provide a tile 400 having a top section 420 joined to a vinyl layer 470, but without a core layer 430. More specifically, in such embodiments, the vinyl layer 470 comprises a solid vinyl material that is structured and disposed to be sufficiently rigid for use as a substrate in flooring applications but also, sufficiently flexible to allow foot comfort for those using the tile 400. Additionally, the vinyl layer 470 may be sufficiently rigid so that an interconnecting mechanism may be profiled thereon, as described further below. The solid vinyl material of the vinyl layer 470 comprises at least a polyvinyl chloride (PVC) material. However, the solid vinyl material of the vinyl layer 470 may also comprise calcium powder or stone dust. In at least one embodiment, the solid vinyl material of the vinyl layer 470 comprises at least a polyvinyl chloride (PVC) material, calcium powder or stone dust, and a plasticizer. As a non-limiting example, plasticizers commonly referred to as DOTP or dioctyl terephthalate may be used. Other examples of plasticizers that may be used include those that do not comprise phthalate.

The following examples of the material composition of the vinyl layer 470 are provided for illustration purposes only, and are not to be considered limiting, as other variations are possible depending on the specific application. For example, the polyvinyl chloride material may be provided in an amount that is about 20% to about 30% of the overall weight of the vinyl layer 470. Also as an example, the calcium powder or stone dust may be provided in an amount that is about 60% to about 70% of the overall weight of the vinyl layer 470. As a further example, the plasticizer may be provided in an amount that is about 10% to about 15% of the overall weight of the vinyl layer 470. In at least one embodiment, the inventive tile 400 comprises a vinyl layer 470 with a vinyl material comprising (i) polyvinyl chloride in an amount that is about 25% of the overall weight of the vinyl layer 470, (ii) calcium powder or stone dust in an amount that is about 63% to about 65% of the overall weight of the vinyl layer 470, and (iii) a plasticizer in an amount that is about 10% to about 12% of the overall weight of the vinyl layer 470.

In one or more preferred embodiments, the vinyl layer 470 of the inventive tile 400 such as is illustrated in FIGS. 33A to 39, comprises a density of about 1,700 kg/m³ (about 106.128 lb/ft³) to about 2,100 kg/m³ (about 131.099 lb/ft³). Favorable results have been observed with a density of the vinyl layer 470 of about 1,800 kg/m³ (about 112.370 lb/ft³) to about 2,000 kg/m³ (about 124.856 lb/ft³) but acceptable results are achievable at densities somewhat outside of this range, as noted above. In one most preferred embodiment, however, the density of the vinyl layer 470 comprises about 1,900 kg/m³ (about 118.613 lb/ft³). Additionally, in those embodiments of the invention including a core layer 430 in addition to the vinyl layer 470, such as is shown in FIGS. 33A to 35B and FIG. 39, the density of the core layer 430

35

may vary according to the specific substrate, i.e., stone plastic composite (SPC) or a densified foam material. In embodiments where the core layer 430 comprises a stone plastic composite material, the density of the core layer 430 may be about 1,500 kg/m³ (about 94.642 lb/ft³) to about 2,200 kg/m³ (about 137.342 lb/ft³).

Still referring to the embodiments illustrated in FIGS. 33A to 39, the overall thickness of the inventive tile 400 can vary according to the specific application. For example, the overall thickness of the tile 400 may range from about 3.5 millimeters (about 0.138 inches) to about 7 millimeters (about 0.276 inches). In embodiments of the tile 400 comprising a core layer 430, the thickness of the core layer 430 may be about 2 millimeters (about 0.079 inches) to about 3 millimeters (about 0.118 inches). The thickness of the vinyl layer 470 may generally be about 1.5 millimeters (0.059 inches) to about 3.0 millimeters (about 0.118 inches). In at least one embodiment, the thickness of the vinyl layer 470 may be about 1 millimeter (about 0.039 inches) to about 2 millimeters (about 0.079 inches). The thickness of the first wear layer 450 and/or second wear layer 440 may be in a range from about 0.1 millimeters (about 0.004 inches) to about 0.7 millimeters (about 0.028 millimeters). The thickness of the decorative layer(s) 460 and/or 490 may be about 0.05 millimeters (about 0.002 inches) to about 0.1 millimeters (about 0.004 inches). In at least some embodiments, the combined thickness of the wear layer(s) 450 and/or 440, and the decorative layer 460 and/or 490, may be about 0.07 millimeters (about 0.003 inches) to about 0.7 millimeters (about 0.028 inches).

As shown in FIGS. 33A-35B and 38, the inventive tile 400 also comprises at least one exposed portion 18 formed on at least one of its sides 16, which, as described herein, is structured to represent an imitation grout line. However, and as shown in FIGS. 35A, 35B and 38, an exposed portion 18' may also be formed on a middle section 28 of the tile 400. Additionally, and as represented in FIGS. 33A-33B and 35A to 38, the exposed portion(s) 18 and/or 18' may be formed on the top section 420 of the tile 400. In FIGS. 33B, 35B and 36B, the exposed portion(s) 18 and/or 18' is illustrated as being formed on the second wear layer 440. This exposes at least a portion of the second wear layer 440 such that an intended grout color of the second decorative layer 490 may be observed there-through. Further, the second wear layer 440 may be configured to closely approximate the texture of a real grout line. For example, the wear layer 440 may be profiled with cutting knives, saws, or other tools, to result in a texture on the wear layer 440 that closely approximates the look and feel of a real grout line. In an alternative embodiment, as shown in FIG. 34, the exposed portion(s) 18 and/or 18' may be formed directly on the core layer 430, instead of on the top section 420.

With reference now to FIGS. 36A-36B and 37, the inventive tile 400 may additionally comprise an interconnecting mechanism 480. As shown in these Figures, the interconnecting mechanism 480 may be formed on the vinyl layer 470. Alternatively, the interconnecting mechanism 480 may be formed on at least a portion of the vinyl layer 470 and/or a portion of the core layer 430. In another alternative embodiment, the interconnecting mechanism 480 may be formed on at least a portion of the core layer 430. Additionally, it is within the scope of the present invention that the interconnecting mechanism 470 comprise a "click" interconnecting mechanism. As used herein, a "click" interconnecting mechanism may be defined as an interconnecting mechanism comprising a male member 482 and/or a female member 484, which may cooperatively achieve a mating

36

engagement. In at least one embodiment, the male member 482 of one tile 400 may be inserted or otherwise slid into a correspondingly dimensioned female member 484 of another tile 400, thereby forming a mating engagement.

With reference again to FIGS. 36A-36B and 37, further features of the inventive tile 400 comprise forming the exposed portion 18 and/or 18' on a portion of the interconnecting mechanism 480. In embodiments of the inventive tile 400 that do not have a core layer 430, the exposed portion 18 and/or 18' may be formed on at least a portion of the top section 420 above the interconnecting mechanism 480. For example, the illustrative embodiment of FIG. 36 shows a tile 400 with an exposed portion 18 formed on a portion of the top section 420 above the male member 482 of the interconnecting mechanism 480. As a further example, the illustrative embodiment of FIG. 37 shows a tile 400 with an exposed portion 18 formed a portion of the top section 420 above the female member 484 of the interconnecting mechanism 480.

In terms of manufacturing, the inventive tile 400 generally relies on an extrusion process. For example, the vinyl layer 470 may be formed by being extruded. Additionally, in embodiments of the tile 400 that include a core layer 430, the core layer 430 may also be extruded, but preferably, as a separate extrusion from the vinyl layer 470. Thereafter, the vinyl layer 470, the first wear layer 450 and/or second wear layer 440, and/or the decorative layer(s) 460 and/or 490, may be placed in a pressing plate and laminated together under sufficient heat and pressure to create a plank. In embodiments comprising a core layer 430, the core layer 430, the vinyl layer 470, the wear layer(s) 450 and/or 440, the decorative layer(s) 460 and/or 490, may be placed in a pressing plate and laminated together under sufficient heat and pressure to create a plank. The plank(s) may be later cut into desired sizes to create individual tiles, and/or profiled to create an exposed portion(s) 18 and/or 18'.

Additionally, it is within the scope of the present invention to "emboss" the tile 400 to provide a highly realistic natural look. Although it is possible to provide a tile 400 with a surface that imitates various types of natural materials, "embossing" generally provides a flooring tile made of other materials with a highly realistic, natural look and feel of a wood surface. The "embossing" of inventive tile 400 may also be achieved during the manufacturing process. More specifically, "embossing" of the wear layer 450 may be achieved by using a press plate configured to correspond to the pattern of the decorative layer 460. This may be referred to as an "embossed in register" effect, wherein the press plate is configured to form a plurality of "ridges" on the surface of the first wear layer 450. Collectively, the plurality of "ridges" may be configured to substantially correspond to the design pattern of the first decorative layer 460 below. This provides an advantage over other "ridge" patterns that are substantially linear and may not correspond to the design pattern of the first decorative layer 460. Providing a tile 400 with a vinyl layer 470 is generally advantageous to achieve "embossing". The vinyl layer 470 may act as a substrate that is sufficiently malleable to substantially conform, along with the wear layer(s) 450 and/or 440 and the decorative layer(s) 460 and/or 490, to the profile of an intended "ridge" pattern.

With reference now to FIG. 39, the inventive tile 400 is shown in another embodiment comprising a top section 420, a vinyl layer 470, a core layer 430, and an additional vinyl layer 470'. As illustrated in FIG. 39, the additional vinyl layer 470' may be adhered or otherwise joined to the bottom of the core layer 430. In such embodiments where tile 400

includes an additional vinyl layer **470'**, the core layer **430** may comprise a stone plastic composite (SPC) material, as described herein. The additional vinyl layer **470'** serves to enhance the structural properties of the tile **400**. In embodiments of the tile **400** comprising an additional vinyl layer **470'**, the thickness of the vinyl layers **470** and/or **470'** may be about 1 millimeter (about 0.039 inches) to about 2 millimeters (about 0.079 inches). Furthermore, in embodiments of the tile **400** comprising an additional vinyl layer **470'** the density of the vinyl layers **470** and/or **470'** may be generally higher to account for their thicknesses.

Yet additional embodiments of the present invention may be seen with reference to FIGS. **40** and **41**. Depicted in such embodiment is a tile **500** comprised of a core layer **530** having a top layer or top section **520** disposed thereon. Such top section **520** may comprise, for instance, a veneer layer or other layer or coating of material, which may be referred to as (but is not limited to) an enamel coating **521**. More specifically, in the illustrated embodiments of FIGS. **40** and **41**, the top section **520** of the tile **500** may comprise an acrylic and/or a polycrylic coating applied directly onto the core layer **530** via spraying procedures or other similar processes. At least one design element **522** may be disposed on such top section **520**, such as through printing processes, wherein such design element(s) **522** may comprise a texture, groove, impression, undulation, color and/or graphical design, or other feature. For instance, the design element **522** may comprise at least one of the foregoing components in order to imitate the look and feel of a genuine flooring material, such as real stone or wood. In at least one embodiment of the present invention, the top section **520** comprising a veneer layer, other layer of material and/or enamel coating may be approximately one micron in thickness, although other ranges of thickness, both smaller and larger, are envisioned herein.

Still referring to FIGS. **40** and **41**, it may be seen that an additional embodiment of the invention may further comprise a shielding layer **523** disposed thereon. Such a shielding layer **523** may be configured to protect the top section **520** from the absorption of liquids or spills, or from scratches, abrasions, and deformations. Further, in at least one embodiment of the present invention, such shielding layer **523** may be substantially transparent, such that the at least one design element printed onto the veneer layer and/or enamel coating **521** is visible there through.

In at least one embodiment of the present invention, the shielding layer **523** may comprise a topical coating, such as an acrylic solution, which may be applied through spraying procedures or other like processes. Alternatively, such a shielding layer **523** may comprise a wear layer such as those previously discussed. Even further, such a shielding layer **523** may instead comprise a film layer, which itself may comprise a thin sheet of polypropylene, polyvinyl chloride, or some other material akin thereto, such as a thermoplastic polymer or a synthetic plastic polymer. As previously stated, such shielding layer **523** may comprise alternative material compositions and thicknesses dependent upon the intended application of the tile **500**.

As may be seen with continued reference to FIGS. **40** and **41**, in at least one embodiment of the present invention wherein the top section **520** comprises a veneer layer, layer of other material and/or enamel coating, the tile **500** may further comprise at least one exposed portion **18** formed within the core layer **510**. More specifically, such an exposed portion **18** may be profiled, via means already discussed herein, after the application of a coating material as one layer (or more) of the top section **520** onto the core layer

510, and the subsequent application of at least one design element thereon. As may be seen, such an exposed portion **18** may, in at least one embodiment, be disposed in connection with a bevel and/or chamfer **90**, or some other slanted edge formed on the side(s) of the tile, as previously recited herein. As may be understood, in such an embodiment, such an exposed portion **18** may be disposed on at least one edge of the tile, and/or at a middle portion thereof, or otherwise.

With reference now to FIG. **41**, in at least one embodiment of the present invention, such an exposed portion **18** may have a protective coating **540** applied thereon, wherein such protective coating **540** may be configured to protect the same from the absorption of liquids which may be spilled thereon. In at least one embodiment, such a protective coating **540** may comprise a painted coating, or may comprise some other material, whether comprising cement, epoxy, acrylic, urethane, or otherwise, and may function as both a colorant and a sealant. In this manner, it may be understood such a protective coating **540** may be configured to provide the foregoing functional benefits of protecting the grout line from discoloration and/or damage, while likewise providing the exposed portion **18** with a selective coloration. Accordingly, such a protective coating **540** may be disposed to provide the exposed portion **18** with any color which may be deemed suitable for its intended application. For instance, such a protective coating **540** may be selected to match in color with the at least one design element applied onto the top surface.

As may be understood, the embodiments of the present invention depicted in FIGS. **40** and **41** may be formed via a process which may comprise: (a) forming a core layer **510**; (b) applying a top section **520** onto a core layer **510**, wherein the top section **520** comprises a coating of material, which may be referred to as an enamel coating; (c) applying at least one design element onto the top section **520**; (d) profiling at least one exposed portion **18** within the core layer **510**; and (e) applying at least one shielding layer **530** onto the top section **520**; and (f) applying at least one protective coating **540** onto the exposed portion **18**. In this manner, it may be understood the foregoing embodiment of the present invention may be formed more efficiently and at less cost due to a reduction in layers and, by extension, a reduction in requisite materials. With reference now to FIG. **42**, in yet additional embodiments of the present invention the tile **500** may additionally comprise at least one interconnecting mechanism **580**. The interconnecting mechanism **580** may itself comprise two disparate portions configured to fit a corresponding portion disposed on an adjacently disposed tile **500**. For instance, such interconnecting mechanism **580** may comprise a male portion **580a** and a female portion **580b**, each of which may itself comprise a tongue side and a groove side, one portion of a click-lock configuration, or any other configuration now known or hereafter developed. Accordingly, it may be understood such a tile **500** may be configured to allow for mating engagement with other adjacently disposed tiles **500**, thereby facilitating alignment there between, and thus the installation thereof. As previously stated, in at least one embodiment of the present invention, such interconnecting mechanism **580** may be structured to permit slight movement and/or rotation between adjacent tiles, which may permit any such installation to accommodate uneven substrates, such as a slab of concrete that is not perfectly level.

With continued reference to FIG. **42**, it may be seen that such a tile **500** may comprise a top section **520** disposed on or in connection with a core layer **530**, the latter of which may be comprised of any rigid material, such as a densified

foam material, a stone plastic composite material, a wood plastic composite material, a stone polymer composite material, or otherwise. As previously stated, such top section **520** may, in certain embodiments, comprise a polyvinyl chloride (PVC) layer. However, in the embodiment depicted in FIG. **42**, such top section **520** may instead comprise a veneer layer and/or layer of other material, such as a coating of material, which may be referred to herein as (but not limited to) an enamel coating **521** which, as previously stated may comprise in some embodiments an acrylic and/or polycrylic coating applied directly onto the core layer **530**. Disposed on top of such enamel coating **521** may be at least one design element **522**, such as a texture, groove, impression, undulation, color or graphical design, or any feature which may, in certain embodiments, be configured to imitate the look and feel of a genuine flooring material, such as real stone or wood. Such enamel coating **521** and at least one design element **522** may have a shielding layer **523** disposed thereon, coincident with the top surface **510** of the tile, which may be configured to protect the tile **500** from scratches, abrasions, and deformations, and/or from the absorption of liquids. As previously stated, alternative embodiments of such a shielding layer **523** may comprise an acrylic solution, a wear layer such as the one previously discussed herein, or at least one thin sheet of polypropylene, polyvinyl chloride, or some other material akin thereto, such as a thermoplastic polymer or a synthetic plastic polymer. As may be seen, such a tile **500** may further comprise at least one exposed portion **18**, which itself may be disposed in connection with a bevel and/or chamfer **90**.

In accordance with the foregoing, depicted in FIG. **43** a tile **500** having at least two exposed portions **18**, wherein one of such exposed portions **18** is configured not at the edge of the tile **500**, but rather central or middle portion thereof. More specifically, the tile **500** shown in the embodiment depicted in FIG. **43** may comprise a core layer **530**, which itself may comprise, for instance, a stone plastic composite material; however, alternative material compositions of such core layer **530** are envisioned herein. As may be understood, and in connection with at least one embodiment previously recited herein, such exposed portion **18** may extend completely across the top surface **510** of the tile **500** between opposite sides thereof. As may also be seen in FIG. **43**, in the tile **500** may further comprise a top section **520** disposed directly on or in connection with the core layer **530**. Such top section **520** may comprise a veneer layer and/or other layer of material, including a coating of material such as an enamel coating **521**, which itself may comprise, for instance, a polyurethane coating. As may be seen, such an enamel coating **521** may be configured such that the exposed portion **18** is disposed within such enamel coating **521**, or otherwise has such enamel coating **521** disposed thereon.

Further, such a top section **520** may additionally comprise at least one design element **522** applied onto such an enamel coating **521**. As previously stated, such at least one design element **522** may comprise, for instance, at least one, or a plurality of textures, grooves, impressions, undulations, color or graphical designs, or any other feature now known or hereafter developed. Disposed on such an enamel coating

521, and thus such at least one design element **522**, may be a shielding layer **523** which, as previously stated may comprise a topical coating, a wear layer, a film layer of polypropylene and/or polyvinyl chloride, or any other material, whether a thermoplastic polymer, a synthetic plastic polymer, or otherwise.

Since many modifications, variations and changes in detail can be made to the described preferred embodiment of the invention, it is intended that all matters in the foregoing description and shown in the accompanying drawings be interpreted as illustrative and not in a limiting sense. For example, the various ranges given herein as the density of a material or for the depth of thickness of a section of the inventive tile should not be considered as the only possibilities. As another example, when using the words “preferably” or “in a preferred embodiment” and similar language, it is intended to mean one particular embodiment, and it should be appreciated that other embodiments are possible and considered part of the invention herein. Thus, the scope of the invention should be determined by the appended claims and their legal equivalents.

What is claimed is:

1. A tile comprising:

a rigid core layer and a top section;

said top section at least partially defined by at least one layer of a coating material applied to said rigid core layer;

said top section further at least partially defining a top surface of the tile;

said rigid core layer having a first density and said top section having a second density; said first density of said rigid core layer is greater than said second density of said top section;

a plurality of sides at least partially defined by said rigid core layer;

at least one exposed portion defined within said rigid core layer; and

said at least one exposed portion including a design element configured to imitate a grout line.

2. The tile of claim 1, wherein said top section includes a plurality of layers of a coating of material.

3. The tile of claim 1, wherein said at least one layer of a coating material is applied via a method selected from the group consisting of spraying, printing, and painting.

4. The tile of claim 3, wherein said at least one layer of a coating material is applied via a combination of at least two of the methods selected from the group consisting of spraying, printing, and painting.

5. The tile of claim 1, wherein said first density of said of rigid core layer is in the range of about 500 kg/m³ (about 31.214 lb/ft³) to about 2,000 kg/m³ (about 124.856 lb/ft³).

6. The tile of claim 1 wherein said at least one exposed portion is formed along one of said plurality of sides of the tile.

7. The tile of claim 1, wherein said at least one exposed portion is formed on said top surface of the tile.

8. The tile of claim 1, wherein said at least one exposed portion is defined within said top section.

* * * * *