



US 20250275473A1

(19) **United States**

(12) **Patent Application Publication**
Min et al.

(10) **Pub. No.: US 2025/0275473 A1**

(43) **Pub. Date: Aug. 28, 2025**

(54) **LIGHT-EMITTING DEVICE INCLUDING
HETEROCYCLIC COMPOUND,
ELECTRONIC APPARATUS AND
ELECTRONIC EQUIPMENT INCLUDING
THE LIGHT-EMITTING DEVICE, AND THE
HETEROCYCLIC COMPOUND**

G02F 1/1335 (2006.01)
H10K 50/12 (2023.01)
H10K 85/20 (2023.01)
H10K 85/40 (2023.01)
H10K 101/20 (2023.01)

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin-si
(KR)

(72) Inventors: **Hyukgi Min**, Yongin-si (KR); **Tsuyoshi
Naijo**, Yongin-si (KR); **Sungsoo Bae**,
Yongin-si (KR); **Hyosup Shin**,
Yongin-si (KR); **Jiyoung Lee**, Yongin-si
(KR); **Changwoong Chu**, Yongin-si
(KR); **Moran Ha**, Yongin-si (KR)

(73) Assignee: **Samsung Display Co., Ltd.**, Yongin-si
(KR)

(21) Appl. No.: **18/910,177**

(22) Filed: **Oct. 9, 2024**

(30) **Foreign Application Priority Data**

Feb. 27, 2024 (KR) 10-2024-0028156

Publication Classification

(51) **Int. Cl.**
H10K 85/60 (2023.01)
C09K 11/02 (2006.01)

(52) **U.S. Cl.**
CPC *H10K 85/658* (2023.02); *C09K 11/02*
(2013.01); *G02F 1/133514* (2013.01); *H10K*
50/12 (2023.02); *H10K 85/20* (2023.02);
H10K 85/40 (2023.02); *H10K 85/615*
(2023.02); *H10K 85/622* (2023.02); *H10K*
85/654 (2023.02); *H10K 85/6572* (2023.02);
H10K 85/6574 (2023.02); *H10K 85/6576*
(2023.02); *H10K 2101/20* (2023.02)

(57) **ABSTRACT**

Embodiments provide a heterocyclic compound, a light-emitting device including the heterocyclic compound, an electronic apparatus including the light-emitting device, and an electronic equipment including the light-emitting device. The heterocyclic compound includes an electron donor moiety including nitrogen, an electron acceptor moiety including boron, and a spiro core atom, wherein the spiro core atom is bonded to the electron donor moiety via a first bond and a second bond, and the spiro core atom is bonded to the electron acceptor moiety via a third bond and a fourth bond. The first bond, the second bond, the third bond, and the fourth bond are each a single bond, and the heterocyclic compound satisfies at least one of Conditions 1 to 3, which are explained in the specification.

10




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5





FIG. 6C



**LIGHT-EMITTING DEVICE INCLUDING
HETEROCYCLIC COMPOUND,
ELECTRONIC APPARATUS AND
ELECTRONIC EQUIPMENT INCLUDING
THE LIGHT-EMITTING DEVICE, AND THE
HETEROCYCLIC COMPOUND**

CROSS-REFERENCE TO RELATED
APPLICATION(S)

[0001] This application claims priority to and benefits of Korean Patent Application No. 10-2024-0028156 under 35 U.S.C. § 119, filed on Feb. 27, 2024, in the Korean Intellectual Property Office, the entire contents of which are incorporated herein by reference.

BACKGROUND

1. Technical Field

[0002] Embodiments relate to a light-emitting device including a heterocyclic compound, an electronic apparatus and electronic equipment that include the light-emitting device, and the heterocyclic compound.

2. Description of the Related Art

[0003] Light-emitting devices are self-emissive devices that have wide viewing angles, high contrast ratios, short response times, and excellent characteristics in terms of luminance, driving voltage, and response speed.

[0004] In a light-emitting device, a first electrode may be arranged on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode may be sequentially arranged on the first electrode. Holes provided from the first electrode move toward the emission layer through the hole transport region, and electrons provided from the second electrode move toward the emission layer through the electron transport region. Carriers, such as the holes and electrons, recombine in the emission layer to produce excitons. The excitons transition from an excited state to a ground state to thereby generate light.

[0005] It is to be understood that this background of the technology section is, in part, intended to provide useful background for understanding the technology. However, this background of the technology section may also include ideas, concepts, or recognitions that were not part of what was known or appreciated by those skilled in the pertinent art prior to a corresponding effective filing date of the subject matter disclosed herein.

SUMMARY

[0006] Embodiments include a light-emitting device including a heterocyclic compound, an electronic apparatus and electronic equipment that include the light-emitting device, and the heterocyclic compound.

[0007] Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the embodiments of the disclosure.

[0008] According to embodiments, a light-emitting device may include

[0009] a first electrode,

[0010] a second electrode facing the first electrode,

[0011] an interlayer between the first electrode and the second electrode and including an emission layer, and

[0012] a heterocyclic compound including an electron donor moiety including nitrogen, an electron acceptor moiety including boron, and a spiro core atom, wherein

[0013] the spiro core atom may be bonded to the electron donor moiety via a first bond and a second bond,

[0014] the spiro core atom may be bonded to the electron acceptor moiety via a third bond and a fourth bond,

[0015] the first bond, the second bond, the third bond, and the fourth bond may each be a single bond, and

[0016] at least one of Conditions 1 to 3 may be satisfied:

[Condition 1]

[0017] the electron donor moiety includes a group represented by Formula 1A;


[Condition 2]

[0018] the electron acceptor moiety includes a first ring, a second ring, and a third ring each bonded to the boron, the first ring and the third ring are bonded to the spiro core atom, and the first ring and the second ring are linked to each other via a first linking group;

[Condition 3]

[0019] the electron acceptor moiety includes a first ring, a second ring, and a third ring each bonded to the boron, the first ring and the third ring are bonded to the spiro core atom, and the second ring and the third ring are linked to each other via a second linking group;

[Formula 1A]



[0020] In Formula 1A,

[0021] R_{61} to R_{63} may each independently be hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{60} alkyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkenyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkynyl group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkoxy group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkylthio group unsubstituted or substituted with at least one R_{10a} , a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} aryloxy group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} arylthio group unsubstituted or substituted with at least one R_{10a} , —C(Q_1)(Q_2)(Q_3), —Si(Q_1)(Q_2)(Q_3), —N(Q_1)(Q_2), —B(Q_1)(Q_2), —C(=O)(Q_1), —S(=O)₂(Q_1), or —P(=O)(Q_1)(Q_2),

[0022] a61 and a63 may each independently be an integer from 1 to 5,

[0023] a62 may be an integer from 1 to 3,

[0024] * indicates a binding site to a neighboring atom,

[0025] R_{10a} may be:

[0026] hydrogen, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, or a nitro group;

[0027] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₃-C₆₀ carbocyclic group, a C₁-C₆₀ heterocyclic group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), —P(=O)(Q₁₁)(Q₁₂), or any combination thereof;

[0028] a C₃-C₆₀ carbocyclic group, a C₁-C₆₀ heterocyclic group, a C₆-C₆₀ aryloxy group, or a C₆-C₆₀ arylthio group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₆₀ carbocyclic group, a C₁-C₆₀ heterocyclic group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), —P(=O)(Q₂₁)(Q₂₂), or any combination thereof; or

[0029] —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), or —P(=O)(Q₃₁)(Q₃₂), and

[0030] Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ may each independently be hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, or a C₃-C₆₀ carbocyclic group or a C₁-C₆₀ heterocyclic group, each unsubstituted or substituted with deuterium, —F, a cyano group, a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a biphenyl group, or any combination thereof.

[0031] In an embodiment, the emission layer may include a host and a dopant, and the dopant may include the heterocyclic compound.

[0032] In an embodiment, the light-emitting device may further include: a second compound including at least one π electron-deficient nitrogen-containing C₁-C₆₀ heterocyclic group; or a third compound may include a group represented by Formula 3; or a fourth compound that may emit delayed fluorescence; or any combination thereof, wherein the heterocyclic compound, the second compound, the third compound, and the fourth compound may be different from each other, and wherein Formula 3 is explained below.

[0033] In an embodiment, the second compound may include a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, or any combination thereof; and the fourth compound may be a compound including at least one cyclic group including both boron (B) and nitrogen (N) as ring-forming atoms.

[0034] In an embodiment, the emission layer may include: the heterocyclic compound; and the second compound, the third compound, the fourth compound, or any combination thereof; and the emission layer may emit blue light.

[0035] According to embodiments, an electronic apparatus may include the light-emitting device.

[0036] In an embodiment, the electronic apparatus may further include a thin-film transistor, wherein the thin-film

transistor may include a source electrode and a drain electrode, and the first electrode of the light-emitting device may be electrically connected to at least one of the source electrode and the drain electrode.

[0037] In an embodiment, the electronic apparatus may further include a color filter, a color conversion layer, a touch screen layer, a polarizing layer, or any combination thereof.

[0038] According to embodiments, an electronic equipment may include the light-emitting device.


[0039] In an embodiment, the electronic equipment may be a flat panel display, a curved display, a computer monitor, a medical monitor, a television, a billboard, an indoor light, an outdoor light, a signal light, a head-up display, a fully transparent display, a partially transparent display, a flexible display, a rollable display, a foldable display, a stretchable display, a laser printer, a telephone, a mobile phone, a tablet computer, a phablet, a personal digital assistant (PDA), a wearable device, a laptop computer, a digital camera, a camcorder, a viewfinder, a micro display, a three-dimensional (3D) display, a virtual reality display, an augmented reality display, a vehicle, a video wall with multiple displays tiled together, a theater screen, a stadium screen, a phototherapy device, or a signboard.

[0040] According to embodiments, a heterocyclic compound may include an electron donor moiety including nitrogen, an electron acceptor moiety including boron, and a spiro core atom, wherein

[0041] the spiro core atom may be bonded to the electron donor moiety via a first bond and a second bond; the spiro core atom may be bonded to the electron acceptor moiety via a third bond and a fourth bond; the first bond, the second bond, the third bond, and the fourth bond may each be a single bond; and at least one of Conditions 1 to 3 may be satisfied, which are explained herein.

[0042] In an embodiment, the heterocyclic compound may be represented by Formula 1:

[Formula 1]



[0043] In Formula 1,

[0044] T₁ may be C, Si, or Ge,

[0045] ring CY₁ to ring CY₅ may each independently be a C₅-C₃₀ carbocyclic group or a C₁-C₃₀ heterocyclic group,

[0046] T₂₁ may be *—C(Z₁)(Z₂)—*, *—Si(Z₁)(Z₂)—*, *—N(Z₁)—*, *—O—*, or *—S—*,

[0047] T₂₂ may be *—C(Z₃)(Z₄)—*, *—Si(Z₃)(Z₄)—*, *—N(Z₃)—*, *—O—*, or *—S—*,

[0048] R₁ to R₅ and Z₁ to Z₄ may each independently be hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl

group, a cyano group, a nitro group, a C₁-C₆₀ alkyl group unsubstituted or substituted with at least one R_{10a}, a C₂-C₆₀ alkenyl group unsubstituted or substituted with at least one R_{10a}, a C₂-C₆₀ alkynyl group unsubstituted or substituted with at least one R_{10a}, a C₁-C₆₀ alkoxy group unsubstituted or substituted with at least one R_{10a}, a C₁-C₆₀ alkylthio group unsubstituted or substituted with at least one R_{10a}, a C₅-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{10a}, a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a}, a C₆-C₆₀ aryloxy group unsubstituted or substituted with at least one R_{10a}, a C₆-C₆₀ arylthio group unsubstituted or substituted with at least one R_{10a}, —C(Q₁)(Q₂)(Q₃), —Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)₂(Q₁), or —P(=O)(Q₁)(Q₂),

[0049] a₁ to a₅ may each independently be an integer from 1 to 20,

[0050] Ar₁ may be a group represented by Formula 1A, a C₅-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{10a}, or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a},

[0051] Z₁ and Z₂ may optionally be bonded to each other to form a C₃-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a},

[0052] Z₃ and Z₄ may optionally be bonded to each other to form a C₃-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a},

[0053] two or more neighboring groups among R₁ in the number of a₁, R₂ in the number of a₂, R₃ in the number of a₃, R₄ in the number of a₄, R₅ in the number of a₅, Z₁ to Z₄, and Ar₁ may optionally be bonded to each other to form a C₃-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a}, and

[0054] R_{10a} and Q₁ to Q₃ may each be the same as described herein.

[0055] In an embodiment, ring CY₁ to ring CY₅ may each independently be a benzene group, a naphthalene group, an anthracene group, a phenanthrene group, a triphenylene group, a pyrene group, a chrysene group, a cyclopentadiene group, a furan group, a thiophene group, a silole group, an indene group, a fluorene group, an indole group, a carbazole group, a benzofuran group, a dibenzofuran group, a benzothiophene group, a dibenzothiophene group, a benzosilole group, a dibenzosilole group, an azafluorene group, an azacarbazole group, an azadibenzofuran group, an azadibenzothiophene group, an azadibenzosilole group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a phenanthroline group, a pyrrole group, a pyrazole group, an imidazole group, a triazole group, an oxazole group, an isoxazole group, a thiazole group, an isothiazole group, an oxadiazole group, a thiadiazole group, a benzopyrazole group, a benzimidazole group, a benzoxazole group, a benzothiazole group, a benzoxadiazole group, a benzothiadiazole group, a dibenzooxasiline group, a dibenzothiasiline group, a dibenzodihydroazasiline group, a dibenzodi-

hydrodihydrodisiline group, a dibenzodihydrosiline group, a dibenzodioxine group, a dibenzooxathiine group, a dibenzooxazine group, a dibenzopyran group, a dibenzodithiine group, a dibenzothiazine group, a dibenzothiopyran group, a dibenzocyclohexadiene group, a dibenzodihydropyridine group, or a dibenzodihydropyrazine group.

[0056] In an embodiment, T₂₁ may be *—C(Z₁)(Z₂)—** or *—Si(Z₁)(Z₂)—**, and T₂₂ may be *—C(Z₃)(Z₄)—** or *—Si(Z₃)(Z₄)—**.

[0057] In an embodiment, at least one of Conditions 4 and 5 may be satisfied, which are explained below.

[0058] In an embodiment, R₁ to R₅ and Z₁ to Z₄ may each independently be:

[0059] hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₂₀ alkyl group, or a C₁-C₂₀ alkoxy group;

[0060] a C₁-C₂₀ alkyl group or a C₁-C₂₀ alkoxy group, each substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, a C₁-C₁₀ alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or any combination thereof;

[0061] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C₁-C₁₀ alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuran group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuran group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, an azadibenzofuran group, an azadibenzothiophenyl group, an azafluorenyl group, an azadibenzosilolyl group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a

C₁-C₁₀ alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a quinoxalyl group, a quinazolyl group, a cinnolyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzothiazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, —O(Q₃₁), —S(Q₃₁), —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —P(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), —P(=O)(Q₃₁)(Q₃₂), or any combination thereof; or

[0062] —C(Q₁)(Q₂)(Q₃), —Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)₂(Q₁), or —P(=O)(Q₁)(Q₂), and

[0063] Q₁ to Q₃ and Q₃₁ to Q₃₃ may each independently be: hydrogen; deuterium; —F; —Cl; —Br; —I; a hydroxyl group; a cyano group; a nitro group; a C₁-C₆₀ alkyl group; a C₂-C₆₀ alkenyl group; a C₂-C₆₀ alkynyl group; a C₁-C₆₀ alkoxy group; or a C₃-C₆₀ carbocyclic group or a C₁-C₆₀ heterocyclic group, each unsubstituted or substituted with deuterium, —F, a cyano group, a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a biphenyl group, or any combination thereof.

[0064] In an embodiment, Ar₁ may be:

[0065] a group represented by Formula 1A; or

[0066] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C₁-C₁₀ alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a quinoxalyl group, a quinazolyl group, a cinnolyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, an

azadibenzofuranyl group, an azadibenzothiophenyl group, an azafluorenyl group, or an azadibenzosilolyl group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C₁-C₁₀ alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a quinoxalyl group, a quinazolyl group, a cinnolyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzothiazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, —O(Q₃₁), —S(Q₃₁), —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —P(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), —P(=O)(Q₃₁)(Q₃₂), or any combination thereof; and

[0067] Q₃₁ to Q₃₃ may each independently be: hydrogen; deuterium; —F; —Cl; —Br; —I; a hydroxyl group; a cyano group; a nitro group; a C₁-C₆₀ alkyl group; a C₂-C₆₀ alkenyl group; a C₂-C₆₀ alkynyl group; a C₁-C₆₀ alkoxy group; or a C₃-C₆₀ carbocyclic group or a C₁-C₆₀ heterocyclic group, each unsubstituted or substituted with deuterium, —F, a cyano group, a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a biphenyl group, or any combination thereof.

[0068] In an embodiment, Ar₁ may be a group represented by Formula 1A.

[0069] In an embodiment, T₂₁ and T₂₂ may each independently be a group represented by Formula 1B, which is explained below.

[0070] In an embodiment, the heterocyclic compound may be represented by Formula 1-1, which is explained below.

[0071] It is to be understood that the embodiments above are described in a generic and explanatory sense only and not for the purposes of limitation, and the disclosure is not limited to the embodiments described above.

BRIEF DESCRIPTION OF THE DRAWINGS

[0072] The accompanying drawings are included to provide a further understanding of the embodiments, and are incorporated in and constitute a part of this specification. The drawings illustrate embodiments of the disclosure and principles thereof. The above and other aspects and features

of the disclosure will become more apparent by describing in detail embodiments thereof with reference to the accompanying drawings, in which:

[0073] FIG. 1 is a schematic cross-sectional view of a light-emitting device according to an embodiment;

[0074] FIG. 2 is a schematic cross-sectional view of an electronic apparatus according to an embodiment;

[0075] FIG. 3 is a schematic cross-sectional view of an electronic apparatus according to another embodiment; and

[0076] FIG. 4 is a schematic perspective view of an electronic equipment according to an embodiment;

[0077] FIG. 5 is a schematic perspective view of an exterior of a vehicle as an electronic equipment including a light-emitting device according to an embodiment; and

[0078] FIGS. 6A to 6C are each a schematic diagram of an interior of a vehicle according to embodiments.

DETAILED DESCRIPTION OF THE EMBODIMENTS

[0079] The disclosure will now be described more fully hereinafter with reference to the accompanying drawings, in which embodiments are shown. This disclosure may, however, be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the disclosure to those skilled in the art.

[0080] In the drawings, the sizes, thicknesses, ratios, and dimensions of the elements may be exaggerated for ease of description and for clarity. Like reference numbers and/or like reference characters refer to like elements throughout.

[0081] In the description, it will be understood that when an element (or region, layer, part, etc.) is referred to as being “on”, “connected to”, or “coupled to” another element, it can be directly on, connected to, or coupled to the other element, or one or more intervening elements may be present therebetween. In a similar sense, when an element (or region, layer, part, etc.) is described as “covering” another element, it can directly cover the other element, or one or more intervening elements may be present therebetween.

[0082] In the description, when an element is “directly on”, “directly connected to”, or “directly coupled to” another element, there are no intervening elements present. For example, “directly on” may mean that two layers or two elements are disposed without an additional element such as an adhesion element therebetween.

[0083] As used herein, the expressions used in the singular such as “a,” “an,” and “the,” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

[0084] As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. For example, “A and/or B” may be understood to mean “A, B, or A and B.” The terms “and” and “or” may be used in the conjunctive or disjunctive sense and may be understood to be equivalent to “and/or”.

[0085] In the specification and the claims, the term “at least one of” is intended to include the meaning of “at least one selected from the group consisting of” for the purpose of its meaning and interpretation. For example, “at least one of A, B, and C” may be understood to mean A only, B only, C only, or any combination of two or more of A, B, and C, such as ABC, ACC, BC, or CC. When preceding a list of

elements, the term, “at least one of,” modifies the entire list of elements and does not modify the individual elements of the list.

[0086] It will be understood that, although the terms first, second, etc. may be used herein to describe various elements, these elements should not be limited by these terms. These terms are only used to distinguish one element from another element. Thus, a first element could be termed a second element without departing from the teachings of the disclosure. Similarly, a second element could be termed a first element, without departing from the scope of the disclosure.

[0087] The spatially relative terms “below”, “beneath”, “lower”, “above”, “upper”, or the like, may be used herein for ease of description to describe the relations between one element or component and another element or component as illustrated in the drawings. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or operation, in addition to the orientation depicted in the drawings. For example, in the case where a device illustrated in the drawing is turned over, the device positioned “below” or “beneath” another device may be placed “above” another device. Accordingly, the illustrative term “below” may include both the lower and upper positions. The device may also be oriented in other directions and thus the spatially relative terms may be interpreted differently depending on the orientations.

[0088] The terms “about” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the recited value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the recited quantity (for example, the limitations of the measurement system). For example, “about” may mean within one or more standard deviations, or within +20%, +10%, or +5% of the stated value.

[0089] It should be understood that the terms “comprises,” “comprising,” “includes,” “including,” “have,” “having,” “contains,” “containing,” and the like are intended to specify the presence of stated features, integers, steps, operations, elements, components, or combinations thereof in the disclosure, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, or combinations thereof.

[0090] Unless otherwise defined or implied herein, all terms (including technical and scientific terms) used have the same meaning as commonly understood by those skilled in the art to which this disclosure pertains. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and should not be interpreted in an ideal or excessively formal sense unless clearly defined in the specification.

[0091] According to an embodiment, a light-emitting device may include:

[0092] a first electrode;

[0093] a second electrode facing the first electrode;

[0094] an interlayer between the first electrode and the second electrode and including an emission layer; and

[0095] a heterocyclic compound including: an electron donor moiety including nitrogen;

- [0096] an electron acceptor moiety including boron; and a spiro core atom, wherein
- [0097] the spiro core atom may be bonded to the electron donor moiety via a first bond and a second bond,
- [0098] the spiro core atom may be bonded to the electron acceptor moiety via a third bond and a fourth bond,
- [0099] the first bond, the second bond, the third bond, and the fourth bond may each be a single bond, and at least one of Conditions 1 to 3 may be satisfied:

[Condition 1]

[0100] the electron donor moiety includes a group represented by Formula 1A;


[Condition 2]

[0101] the electron acceptor moiety includes a first ring, a second ring, and a third ring each bonded to the boron, the first ring and the third ring are bonded to the spiro core atom, and the first ring and the second ring are linked to each other via a first linking group;

[Condition 3]

[0102] the electron acceptor moiety includes a first ring, a second ring, and a third ring each bonded to the boron, the first ring and the third ring are bonded to the spiro core atom, and the second ring and the third ring are linked to each other via a second linking group;

[Formula 1A]



[0103] In Formula 1A,

- [0104] R_{61} to R_{63} may each independently be hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{60} alkyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkenyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkynyl group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkoxy group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkylthio group unsubstituted or substituted with at least one R_{10a} , a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} aryloxy group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} arylthio group unsubstituted or substituted with at least one R_{10a} , $-C(Q_1)(Q_2)(Q_3)$, $-Si(Q_1)(Q_2)(Q_3)$, $-N(Q_1)(Q_2)$, $-B(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-S(=O)_2(Q_1)$, or $-P(=O)(Q_1)(Q_2)$,
- [0105] $a61$ and $a63$ may each independently be an integer from 1 to 5,
- [0106] $a62$ may be an integer from 1 to 3,

[0107] * indicates a binding site to a neighboring atom, and

[0108] R_{10a} and Q_1 to Q_3 may each independently be the same as described herein.

[0109] In an embodiment,

[0110] the first electrode may be an anode,

[0111] the second electrode may be a cathode,

[0112] the interlayer may further include a hole transport region between the first electrode and the emission layer, and an electron transport region between the emission layer and the second electrode,

[0113] the hole transport region may include a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or any combination thereof, and

[0114] the electron transport region may include a hole blocking layer, an electron transport layer, an electron injection layer, or any combination thereof.

[0115] In embodiments, the interlayer may include the heterocyclic compound.

[0116] In embodiments, the emission layer may include the heterocyclic compound.


[0117] In embodiments, the emission layer of the light-emitting device may include a dopant and a host, and the dopant may include the heterocyclic compound. For example, the heterocyclic compound may serve as a dopant. For example, the emission layer may emit blue light. The blue light may have a maximum emission wavelength in a range of, for example, about 430 nm to about 480 nm.

[0118] In embodiments, the electron transport region of the light-emitting device may include a hole blocking layer, and the hole blocking layer may include a phosphine oxide-containing compound, a silicon-containing compound, or any combination thereof. For example, the hole blocking layer may contact (e.g., directly contact) the emission layer.

[0119] In an embodiment, the light-emitting device may further include: a second compound including at least one π electron-deficient nitrogen-containing C_1 - C_{60} heterocyclic group; or a third compound including a group represented by Formula 3; or a fourth compound that emits delayed fluorescence, or any combination thereof, and

[0120] the heterocyclic compound, the second compound, the third compound, and the fourth compound may be different from each other;

[Formula 3]



[0121] In Formula 3,

[0122] ring CY_{71} and ring CY_{72} may each independently be a π electron-rich C_3 - C_{60} cyclic group or a pyridine group,

[0123] X_{71} may be: a single bond; or a linking group including O, S, N, B, C, Si, or any combination thereof, and

[0124] * indicates a binding site to any atom included in a remaining part of the third compound other than the group represented by Formula 3.

[0125] In an embodiment, the heterocyclic compound may include at least one deuterium.

[0126] In embodiments, the second compound, the third compound, and the fourth compound may each independently include at least one deuterium.

[0127] In embodiments, the second compound may include at least one silicon.

[0128] In embodiments, the third compound may include at least one silicon.

[0129] In embodiments, the light-emitting device may further include the second compound and the third compound, in addition to the heterocyclic compound, and at least one of the second compound and the third compound may each independently include at least one deuterium, at least one silicon, or any combination thereof.

[0130] In an embodiment, the light-emitting device (e.g., the emission layer in the light-emitting device) may further include the second compound, in addition to the heterocyclic compound. At least one of the heterocyclic compound and the second compound may each independently include at least one deuterium. For example, the light-emitting device (e.g., the emission layer in the light-emitting device) may further include the third compound, the fourth compound, or any combination thereof, in addition to the heterocyclic compound and the second compound.

[0131] In embodiments, the light-emitting device (e.g., the emission layer in the light-emitting device) may further include the third compound, in addition to the heterocyclic compound. At least one of the heterocyclic compound and the third compound may each independently include at least one deuterium. For example, the light-emitting device (e.g., the emission layer in the light-emitting device) may further include the second compound, the fourth compound, or any combination thereof, in addition to the heterocyclic compound and the third compound.

[0132] In embodiments, the light-emitting device (e.g., the emission layer in the light-emitting device) may further include the fourth compound, in addition to the heterocyclic compound. At least one of the heterocyclic compound and the fourth compound may each independently include at least one deuterium. The fourth compound may improve the color purity, luminescence efficiency, and lifespan characteristics of the light-emitting device. For example, the light-emitting device (e.g., the emission layer in the light-emitting device) may further include the second compound, the third compound, or any combination thereof, in addition to the heterocyclic compound and the fourth compound.

[0133] In embodiments, the light-emitting device (e.g., the emission layer in the light-emitting device) may further include the second compound and the third compound, in addition to the heterocyclic compound. The second compound and the third compound may form an exciplex. At least one of the heterocyclic compound, the second compound, and the third compound may each independently include at least one deuterium.


[0134] In embodiments, the emission layer of the light-emitting device may include: the heterocyclic compound; and the second compound, the third compound, the fourth compound, or any combination thereof; and the emission layer may emit blue light.

[0135] In embodiments, the blue light may have a maximum emission wavelength in a range of about 430 nm to about 480 nm. For example, the blue light may have a maximum emission wavelength in a range of about 430 nm

to about 475 nm. For example, the blue light may have a maximum emission wavelength in a range of about 440 nm to about 475 nm. For example, the blue light may have a maximum emission wavelength in a range of about 450 nm to about 475 nm. For example, the blue light may have a maximum emission wavelength in a range of about 430 nm to about 470 nm. For example, the blue light may have a maximum emission wavelength in a range of about 440 nm to about 470 nm. For example, the blue light may have a maximum emission wavelength in a range of about 450 nm to about 470 nm. For example, the blue light may have a maximum emission wavelength in a range of about 430 nm to about 465 nm. For example, the blue light may have a maximum emission wavelength in a range of about 440 nm to about 465 nm. For example, the blue light may have a maximum emission wavelength in a range of about 450 nm to about 465 nm. For example, the blue light may have a maximum emission wavelength in a range of about 430 nm to about 460 nm. For example, the blue light may have a maximum emission wavelength in a range of about 440 nm to about 460 nm. For example, the blue light may have a maximum emission wavelength in a range of about 450 nm to about 460 nm.

[0136] In an embodiment, the second compound may include a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, or any combination thereof.

[0137] In embodiments, the third compound may not include CBP or mCBP:



[0138] In an embodiment, the fourth compound may be a compound in which a difference between a triplet energy level (eV) and a singlet energy level (eV) may be in a range of about 0 eV to about 0.5 eV. For example, the fourth compound may be a compound in which a difference between a triplet energy level (eV) and a singlet energy level (eV) may be in a range of about 0 eV to about 0.3 eV.

[0139] In embodiments, the fourth compound may be a compound including at least one cyclic group including both boron (B) and nitrogen (N) as ring-forming atoms.

[0140] In embodiments, the fourth compound may be a C_8 - C_{60} polycyclic group-containing compound including two or more cyclic groups that are condensed with each other while sharing B.


[0141] In embodiments, the fourth compound may include a condensed ring in which at least one third ring is condensed with at least one fourth ring,

[0142] wherein the third ring may be a cyclopentane group, a cyclohexane group, a cycloheptane group, a cyclooctane group, a cyclopentene group, a cyclohexene group, a cycloheptene group, a cyclooctene group, an adamantane group, a norbornene group, a norbornane group, a bicyclo[1.1.1] pentane group, a bicyclo[2.1.1] hexane group, a bicyclo[2.2.2] octane group, a benzene group, a pyridine group, a pyrimidine group, a pyridazine group, a pyrazine group, or a triazine group, and

[0143] the fourth ring may be a 1,2-azaborinine group, a 1,3-azaborinine group, a 1,4-azaborinine group, a 1,2-dihydro-1,2-azaborinine group, a 1,4-oxaborinine group, a 1,4-thiaborinine group, or a 1,4-dihydroborinine group.

[0144] In an embodiment, the third compound may not include a compound represented by Formula 3-1 as described herein.

[0145] In an embodiment, the second compound may include a compound represented by Formula 2:



[0146] In Formula 2,

[0147] L_{51} to L_{53} may each independently be a single bond, a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,


[0148] b_{51} to b_{53} may each independently be an integer from 1 to 5,

[0149] X_{54} may be N or C(R_{54}), X_{55} may be N or C(R_{55}), X_{56} may be N or C(R_{56}), and at least one of X_{54} to X_{56} may each be N, and


[0150] R_{51} to R_{56} and R_{10a} may each be the same as described herein.

[0151] In embodiments, the third compound may include a compound represented by Formula 3-1, a compound represented by Formula 3-2, a compound represented by Formula 3-3, a compound represented by Formula 3-4, a compound represented by Formula 3-5, or any combination thereof:


[Formula 3-1]




[Formula 3-2]




[Formula 3-3]



[Formula 3-4]





[Formula 3-5]



[0152] In Formulae 3-1 to 3-5,

[0153] ring CY_{71} to ring CY_{74} may each independently be a π electron-rich C_3 - C_{60} cyclic group or a pyridine group,

- [0154] X_{82} may be a single bond, O, S, N—[(L_{82}) $_{b82}$ — R_{82}], C(R_{82a})(R_{82b}), or Si(R_{82a})(R_{82b}),
- [0155] X_{83} may be a single bond, O, S, N—[(L_{83}) $_{b83}$ — R_{83}], C(R_{83a})(R_{83b}), or Si(R_{83a})(R_{83b}),
- [0156] X_{84} may be O, S, N—[(L_{84}) $_{b84}$ — R_{84}], C(R_{84a})(R_{84b}), or Si(R_{84a})(R_{84b}),
- [0157] X_{85} may be C or Si,
- [0158] L_{81} to L_{85} may each independently be a single bond, *—C(Q_4)(Q_5)—**, *—Si(Q_4)(Q_5)—**, a π electron-rich C_3 — C_{60} cyclic group unsubstituted or substituted with at least one R_{10a} , or a pyridine group unsubstituted or substituted with at least one R_{10a} , wherein Q_4 and Q_5 may each independently be the same as described in connection with Q_1 ,
- [0159] $b81$ to $b85$ may each independently be an integer from 1 to 5,
- [0160] R_{71} to R_{74} , R_{81} to R_{85} , R_{82a} , R_{82b} , R_{83a} , R_{83b} , R_{84a} , and R_{84b} are each the same as described herein,
- [0161] $a71$ to $a74$ may each independently be an integer from 0 to 20, and
- [0162] R_{10a} is the same as described herein.
- [0163] In embodiments, the fourth compound may include a compound represented by Formula 502, a compound represented by Formula 503, or any combination thereof:



- [0164] In Formulae 502 and 503,
- [0165] ring A_{501} to ring A_{504} may each independently be a C_3 — C_{60} carbocyclic group or a C_1 — C_{60} heterocyclic group,
- [0166] Y_{505} may be O, S, N(R_{505}), B(R_{505}), C(R_{505a})(R_{505b}), or Si(R_{505a})(R_{505b}),
- [0167] Y_{506} may be O, S, N(R_{506}), B(R_{506}), C(R_{506a})(R_{506b}), or Si(R_{506a})(R_{506b}),
- [0168] Y_{507} may be O, S, N(R_{507}), B(R_{507}), C(R_{507a})(R_{507b}), or Si(R_{507a})(R_{507b}),
- [0169] Y_{508} may be O, S, N(R_{508}), B(R_{508}), C(R_{508a})(R_{508b}), or Si(R_{508a})(R_{508b}),
- [0170] Y_{51} and Y_{52} may each independently be B, P(=O), or S(=O),

- [0171] R_{500a} , R_{500b} , R_{501} to R_{508} , R_{505a} , R_{505b} , R_{506a} , R_{506b} , R_{507a} , R_{507b} , R_{508a} , and R_{508b} are each the same as described herein, and

- [0172] $a501$ to $a504$ may each independently be an integer from 0 to 20.

- [0173] The light-emitting device may have a structure according to a first embodiment or a second embodiment.

First Embodiment

[0174] According to a first embodiment, the heterocyclic compound may be included in the emission layer in the interlayer of the light-emitting device, wherein the emission layer may further include a host. The heterocyclic compound and the host may be different from each other, and the emission layer may emit phosphorescence or fluorescence (e.g., delayed fluorescence) emitted from the heterocyclic compound. For example, according to the first embodiment, the heterocyclic compound may be a dopant or an emitter. For example, the heterocyclic compound may be a fluorescent dopant or a fluorescence emitter.

[0175] Phosphorescence or fluorescence emitted from the heterocyclic compound may be blue light.

[0176] The emission layer may further include an auxiliary dopant. The auxiliary dopant may improve the luminescence efficiency from the heterocyclic compound by effectively transferring energy to the heterocyclic compound, which may be a dopant or an emitter.

[0177] The auxiliary dopant may be different from each of the heterocyclic compound and the host.

[0178] In an embodiment, the auxiliary dopant may be a compound emitting delayed fluorescence.

[0179] In embodiments, the auxiliary dopant may be a compound that includes at least one cyclic group including both boron (B) and nitrogen (N) as ring-forming atoms.

Second Embodiment

[0180] According to a second embodiment, the heterocyclic compound may be included in the emission layer in the interlayer of the light-emitting device, wherein the emission layer may further include a host and a dopant. The heterocyclic compound, the host, and the dopant may be different from each other, and the emission layer may emit phosphorescence or fluorescence (e.g., delayed fluorescence) emitted from the dopant.

[0181] In an embodiment, the heterocyclic compound in the second embodiment may not serve as a dopant, and may serve as an auxiliary dopant or as a sensitizer that transfers energy to a dopant (or emitter).

[0182] In embodiments, the heterocyclic compound in the second embodiment may serve as an emitter and may also serve as an auxiliary dopant (or sensitizer) that transfers energy to a dopant (or emitter).

[0183] For example, phosphorescence or fluorescence emitted from the dopant (or emitter) in the second embodiment may be blue phosphorescence or blue fluorescence (e.g., blue delayed fluorescence).

[0184] The dopant (or emitter) in the second embodiment may be a phosphorescent dopant material (e.g., an organometallic compound represented by Formula 401) or any fluorescent dopant material (e.g., the heterocyclic compound, a compound represented by Formula 501, a compound represented by Formula 502, a compound represented by Formula 503, or any combination thereof).

[0185] The blue light in the first embodiment and the second embodiment may be blue light having a maximum emission wavelength in a range of about 390 nm to about 500 nm. For example, the blue light may have a maximum emission wavelength in a range of about 410 nm to about 490 nm. For example, the blue light may have a maximum emission wavelength in a range of about 430 nm to about 480 nm. For example, the blue light may have a maximum emission wavelength in a range of about 440 nm to about 475 nm. For example, The blue light may have a maximum emission wavelength in a range of about 455 nm to about 470 nm.

[0186] The auxiliary dopant or the sensitizer in the first embodiment may include, for example, the fourth compound represented by Formula 502 or Formula 503.

[0187] In an embodiment, the host in the first embodiment and the second embodiment may be any host material (e.g., a compound represented by Formula 301, a compound represented by 301-1, a compound represented by Formula 301-2, or any combination thereof).

[0188] In embodiments, the host in the first embodiment and the second embodiment may be the second compound, the third compound, or any combination thereof.

[0189] In embodiments, the light-emitting device may further include a capping layer outside the first electrode and/or a capping layer outside the second electrode.

[0190] In embodiments, the light-emitting device may further include at least one of a first capping layer outside the first electrode and a second capping layer outside the second electrode, and the heterocyclic compound may be included in at least one of the first capping layer and the second capping layer. The first capping layer and/or the second capping layer may be the same as described herein.

[0191] In an embodiment, the light-emitting device may include:

[0192] a first capping layer outside the first electrode and including the heterocyclic compound;

[0193] a second capping layer outside the second electrode and including the heterocyclic compound; or

[0194] the first capping layer and the second capping layer.

[0195] The expression “(an interlayer and/or a capping layer) includes a heterocyclic compound represented by Formula 1” as used herein may include an embodiment in which “(an interlayer and/or a capping layer) includes identical heterocyclic compounds represented by Formula 1” and an embodiment in which “(an interlayer and/or a capping layer) includes two or more different heterocyclic compounds each independently represented by Formula 1.”

[0196] In an embodiment, the interlayer and/or the capping layer may include, as the heterocyclic compound, Compound 1 only. For example, Compound 1 may be present in the emission layer of the light-emitting device. In embodiments, the interlayer may include, as the heterocyclic compound, Compounds 1 and 2. For example, Compounds 1 and 2 may be present in a same layer (e.g., both Compounds 1 and 2 may be present in the emission layer), or may be present in different layers (e.g., Compound 1 may be present in the emission layer, and Compound 2 may be present in the electron transport region).

[0197] The term “interlayer” as used herein refers to a single layer and/or all layers between the first electrode and the second electrode of the light-emitting device.

[0198] According to an embodiment, an electronic apparatus may include the light-emitting device. The electronic apparatus may further include a thin-film transistor. In an embodiment, the electronic apparatus may further include a thin-film transistor including a source electrode and a drain electrode, and the first electrode of the light-emitting device may be electrically connected to at least one of the source electrode and the drain electrode. In an embodiment, the electronic apparatus may further include a color filter, a color conversion layer, a touch screen layer, a polarizing layer, or any combination thereof. The electronic apparatus may be the same as described herein.

[0199] According to an embodiment, an electronic equipment may include the light-emitting device.

[0200] In an embodiment, the electronic equipment may be a flat panel display, a curved display, a computer monitor, a medical monitor, a television, a billboard, an indoor light, an outdoor light, a signal light, a head-up display, a fully transparent display, a partially transparent display, a flexible display, a rollable display, a foldable display, a stretchable display, a laser printer, a telephone, a mobile phone, a tablet computer, a phablet, a personal digital assistant (PDA), a wearable device, a laptop computer, a digital camera, a camcorder, a viewfinder, a micro display, a three-dimensional (3D) display, a virtual reality display, an augmented reality display, a vehicle, a video wall with multiple displays tiled together, a theater screen, a stadium screen, a phototherapy device, or a signboard.

[0201] Embodiments provide a heterocyclic compound, which may be the same as described herein.

[0202] Synthesis methods of the heterocyclic compound may be recognizable by one of ordinary skill in the art by referring to the Synthesis Examples and/or the Examples provided below.

[0203] [Description of heterocyclic compound]

[0204] According to an embodiment, a heterocyclic compound may include: an electron donor moiety including nitrogen; an electron acceptor moiety including boron; and a spiro core atom, wherein

[0205] the spiro core atom may be bonded to the electron donor moiety via a first bond and a second bond, and the spiro core atom may be bonded to the electron acceptor moiety via a third bond and a fourth bond,

[0206] the first bond, the second bond, the third bond, and the fourth bond may each be a single bond, and at least one of Conditions 1 to 3 may be satisfied:

[Condition 1]

[0207] the electron donor moiety includes a group represented by Formula 1A;

[Condition 2]


[0208] the electron acceptor moiety includes a first ring, a second ring, and a third ring each bonded to the boron, the first ring and the third ring are bonded to the spiro core atom, and the first ring and the second ring are linked to each other via a first linking group;

[Condition 3]

[0209] the electron acceptor moiety includes a first ring, a second ring, and a third ring each bonded to the boron, the

first ring and the third ring are bonded to the spiro core atom, and the second ring and the third ring are linked to each other via a second linking group;

[Formula 1A]



[0210] In Formula 1A,

[0211] R_{61} to R_{63} may each independently be hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{60} alkyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkenyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkynyl group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkoxy group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkylthio group unsubstituted or substituted with at least one R_{10a} , a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} aryloxy group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} arylthio group unsubstituted or substituted with at least one R_{10a} , $-C(Q_1)(Q_2)(Q_3)$, $-Si(Q_1)(Q_2)(Q_3)$, $-N(Q_1)(Q_2)$, $-B(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-S(=O)_2(Q_1)$, or $-P(=O)(Q_1)(Q_2)$,

[0212] a_{61} and a_{63} may each independently be an integer from 1 to 5,

[0213] a_{62} may be an integer from 1 to 3,

[0214] * indicates a binding site to a neighboring atom,

[0215] R_{10a} may be:

[0216] hydrogen, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, or a nitro group;

[0217] a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, or a C_1 - C_{60} alkoxy group, each unsubstituted or substituted with deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, a C_5 - C_{60} carbocyclic group, a C_1 - C_{60} heterocyclic group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, $-Si(Q_{11})(Q_{12})(Q_{13})$, $-N(Q_{11})(Q_{12})$, $-B(Q_{11})(Q_{12})$, $-C(=O)(Q_{11})$, $-S(=O)_2(Q_{11})$, $-P(=O)(Q_{11})(Q_{12})$, or any combination thereof;

[0218] a C_3 - C_{60} carbocyclic group, a C_1 - C_{60} heterocyclic group, a C_6 - C_{60} aryloxy group, or a C_6 - C_{60} arylthio group, each unsubstituted or substituted with deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{60} carbocyclic group, a C_1 - C_{60} heterocyclic group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, $-Si(Q_{21})(Q_{22})(Q_{23})$, $-N(Q_{21})(Q_{22})$, $-B(Q_{21})(Q_{22})$, $-C(=O)(Q_{21})$, $-S(=O)_2(Q_{21})$, $-P(=O)(Q_{21})(Q_{22})$, or any combination thereof; or

[0219] $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{31})(Q_{32})$, $-B(Q_{31})(Q_{32})$, $-C(=O)(Q_{31})$, $-S(=O)_2(Q_{31})$, or $-P(=O)(Q_{31})(Q_{32})$, and

[0220] Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} may each independently be: hydrogen; deuterium; $-F$; $-Cl$; $-Br$; $-I$; a hydroxyl group; a cyano group; a nitro group; a C_1 - C_{60} alkyl group; a C_2 - C_{60} alkenyl group; a C_2 - C_{60} alkynyl group; a C_1 - C_{60} alkoxy group; or a C_3 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group, each unsubstituted or substituted with deuterium, $-F$, a cyano group, a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a biphenyl group, or any combination thereof.

[0221] In Formula 1A, a_{61} to a_{63} respectively indicate the number of R_{61} to the number of R_{63} . When a_{61} is 2 or more, two or more of R_{61} may be identical to or different from each other, when a_{62} is 2 or more, two or more of R_{62} may be identical to or different from each other, and when a_{63} is 2 or more, two or more of R_{63} may be identical to or different from each other.

[0222] In an embodiment, the heterocyclic compound may satisfy Conditions 2 and 3.

[0223] In an embodiment, the heterocyclic compound may satisfy all of Conditions 1 to 3.

[0224] In an embodiment, the spiro core atom may be C, Si, or Ge.

[0225] In an embodiment, the spiro core atom may be Si or Ge.

[0226] In Conditions 2 and 3,

[0227] the first linking group may be $^*C(Z_1)(Z_2)^{**}$, $^*Si(Z_1)(Z_2)^{**}$, $^*N(Z_1)^{**}$, $^*O^{**}$, or $^*S^{**}$,

[0228] the second linking group may be $^*C(Z_3)(Z_4)^{**}$, $^*Si(Z_3)(Z_4)^{**}$, $^*N(Z_3)^{**}$, $^*O^{**}$, or $^*S^{**}$,

[0229] Z_1 to Z_4 may each independently be hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{60} alkyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkenyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkynyl group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkoxy group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkylthio group unsubstituted or substituted with at least one R_{10a} , a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} aryloxy group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} arylthio group unsubstituted or substituted with at least one R_{10a} , $-C(Q_1)(Q_2)(Q_3)$, $-Si(Q_1)(Q_2)(Q_3)$, $-N(Q_1)(Q_2)$, $-B(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-S(=O)_2(Q_1)$, or $-P(=O)(Q_1)(Q_2)$,


[0230] Z_1 and Z_2 may optionally be bonded to each other to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , and

[0231] Z_3 and Z_4 may optionally be bonded to each other to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} .

[0232] R_{10a} and Q_1 to Q_3 may each be the same as described herein.

[0233] In an embodiment, the heterocyclic compound may be represented by Formula 1:

[Formula 1]



[0234] In Formula 1,

[0235] T_1 may be C, Si, or Ge,

[0236] ring CY_1 to ring CY_5 may each independently be a C_5 - C_{80} carbocyclic group or a C_1 - C_{30} heterocyclic group,

[0237] T_{21} may be $^*C(Z_1)(Z_2)^*$, $^*Si(Z_1)(Z_2)^*$, $^*N(Z_1)^*$, $^*O^*$, or $^*S^*$, T_{22} may be $^*C(Z_3)(Z_4)^*$, $^*Si(Z_3)(Z_4)^*$, $^*N(Z_3)^*$, $^*O^*$, or $^*S^*$,

[0238] R_1 to R_5 and Z_1 to Z_4 may each independently be hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{60} alkyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkenyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkynyl group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkoxy group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkylthio group unsubstituted or substituted with at least one R_{10a} , a C_5 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} aryloxy group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} arylthio group unsubstituted or substituted with at least one R_{10a} , $-C(Q_1)(Q_2)(Q_3)$, $-Si(Q_1)(Q_2)(Q_3)$, $-N(Q_1)(Q_2)$, $-B(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-S(=O)_2(Q_1)$, or $-P(=O)(Q_1)(Q_2)$,

[0239] a_1 to a_5 may each independently be an integer from 1 to 20,

[0240] Ar_1 may be a group represented by Formula 1A, a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,

[0241] Z_1 and Z_2 may optionally be bonded to each other to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,

[0242] Z_3 and Z_4 may optionally be bonded to each other to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,

[0243] two or more neighboring groups among R_1 in the number of a_1 , R_2 in the number of a_2 , R_3 in the number of a_3 , R_4 in the number of a_4 , R_5 in the number of a_5 ,

Z_1 to Z_4 , and Ar_1 may optionally be bonded to each other to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , and

[0244] R_{10a} and Q_1 to Q_3 may each be the same as described herein.

[0245] In an embodiment, T_1 may be Si or Ge.

[0246] In an embodiment, ring CY_1 to ring CY_5 may each independently be:

[0247] a benzene group, a naphthalene group, an anthracene group, a phenanthrene group, a triphenylene group, a pyrene group, a chrysene group, a cyclopentadiene group, a furan group, a thiophene group, a silole group, an indene group, a fluorene group, an indole group, a carbazole group, a benzofuran group, a dibenzofuran group, a benzothiophene group, a dibenzothiophene group, a benzosilole group, a dibenzosilole group, an azafluorene group, an azacarbazole group, an azadibenzofuran group, an azadibenzothiophene group, an azadibenzosilole group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a phenanthroline group, a pyrrole group, a pyrazole group, an imidazole group, a triazole group, an oxazole group, an isoxazole group, a thiazole group, an isothiazole group, an oxadiazole group, a thiadiazole group, a benzopyrazole group, a benzimidazole group, a benzoxazole group, a benzothiazole group, a benzoxadiazole group, a benzothiadiazole group, a dibenzooxasiline group, a dibenzothiasilene group, a dibenzodihydroazasilene group, a dibenzodihydrodihydrodisilene group, a dibenzodihydrodisilene group, a dibenzodioxine group, a dibenzooxathiine group, a dibenzooxazine group, a dibenzopyran group, a dibenzodithiine group, a dibenzothiazine group, a dibenzothiopyran group, a dibenzocyclohexadiene group, a dibenzodihydropyridine group, or a dibenzodihydropyrazine group.

[0248] In an embodiment, ring CY_1 to ring CY_5 may each independently be a benzene group, a pyridine group, a pyrimidine group, a naphthalene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, a fluorene group, or a dibenzosilole group.

[0249] In an embodiment, ring CY_1 to ring CY_5 may each be a benzene group.

[0250] In an embodiment, T_{21} may be $^*C(Z_1)(Z_2)^*$ or $^*Si(Z_1)(Z_2)^*$, and

[0251] T_{22} may be $^*C(Z_3)(Z_4)^*$ or $^*Si(Z_3)(Z_4)^*$,

[0252] In an embodiment, the heterocyclic compound represented by Formula 1 may satisfy at least one of Conditions 4 and 5:

[Condition 4]

[0253] Z_1 and Z_2 are bonded to each other to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ;

[Condition 5]

[0254] Z_3 and Z_4 are bonded to each other to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} .

[0255] In an embodiment, the heterocyclic compound represented by Formula 1 may satisfy both Conditions 4 and 5.

[0256] In an embodiment, R_1 to R_5 and Z_1 to Z_4 may each independently be:

[0257] hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, or a C_1 - C_{20} alkoxy group;

[0258] a C_1 - C_{20} alkyl group or a C_1 - C_{20} alkoxy group, each substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{10} alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or any combination thereof;

[0259] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, an azadibenzofuranlyl group, an azadibenzothiophenyl group, an azafluorenyl group, or an azadibenzosilolyl group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a

pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, a benzothiazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, —O(Q_{31}), —S(Q_{31}), —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —P(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), —P(=O)(Q_{31})(Q_{32}), or any combination thereof; or

[0260] —C(Q_1)(Q_2)(Q_3), —Si(Q_1)(Q_2)(Q_3), —N(Q_1)(Q_2), —B(Q_1)(Q_2), —C(=O)(Q_1), —S(=O)₂(Q_1), or —P(=O)(Q_1)(Q_2), and

[0261] Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be: hydrogen; deuterium; —F; —Cl; —Br; —I; a hydroxyl group; a cyano group; a nitro group; a C_1 - C_{60} alkyl group; a C_2 - C_{60} alkenyl group; a C_2 - C_{60} alkynyl group; a C_1 - C_{60} alkoxy group; or a C_3 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group, each unsubstituted or substituted with deuterium, —F, a cyano group, a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a biphenyl group, or any combination thereof.

[0262] In an embodiment, R_1 to R_5 and Z_1 to Z_4 may each independently be:

[0263] hydrogen, deuterium, —F, a C_1 - C_{20} alkyl group, or a C_1 - C_{20} alkoxy group;

[0264] a C_1 - C_{20} alkyl group or a C_1 - C_{20} alkoxy group, each substituted with deuterium, —F, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a C_1 - C_{10} alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or any combination thereof;

[0265] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, a dibenzofuranlyl group, or a dibenzothiophenyl group, each unsubstituted or substituted with deuterium, —F, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a

phenyl group, a biphenyl group, a C₁-C₁₀ alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuran group, a benzothiophenyl group, a dibenzofuran group, a dibenzothiophenyl group, —O(Q₃₁), —S(Q₃₁), —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), or any combination thereof; or —C(Q₁)(Q₂)(Q₃), —Si(Q₁)(Q₂)(Q₃), or —N(Q₁)(Q₂), and

[0266] Q₁ to Q₃ and Q₃₁ to Q₃₃ may each independently be: hydrogen; deuterium; —F; a C₁-C₆₀ alkyl group; a C₂-C₆₀ alkenyl group; a C₂-C₆₀ alkynyl group; a C₁-C₆₀ alkoxy group; or a C₃-C₆₀ carbocyclic group or a C₁-C₆₀ heterocyclic group, each unsubstituted or substituted with deuterium, —F, a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a biphenyl group, or any combination thereof.

[0267] In an embodiment, R₁ to R₅ and Z₁ to Z₄ may each independently be:

[0268] hydrogen, deuterium, or a C₁-C₂₀ alkyl group;

[0269] a C₁-C₂₀ alkyl group substituted with deuterium, —CD₃, —CD₂H, —CDH₂, a C₁-C₁₀ alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclohexenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a naphthyl group, or any combination thereof;

[0270] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C₁-C₁₀ alkylphenyl group, or a naphthyl group, each unsubstituted or substituted with deuterium, —CD₃, —CD₂H, —CDH₂, a C₁-C₂₀ alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C₁-C₁₀ alkylphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), or any combination thereof; or —C(Q₁)(Q₂)(Q₃) or —Si(Q₁)(Q₂)(Q₃), and

[0271] Q₁ to Q₃ and Q₃₁ to Q₃₃ may each independently be: hydrogen; deuterium; a C₁-C₆₀ alkyl group; a C₂-C₆₀ alkenyl group; a C₂-C₆₀ alkynyl group; or a C₃-C₆₀ carbocyclic group unsubstituted or substituted with deuterium, a C₁-C₆₀ alkyl group, a phenyl group, a biphenyl group, or any combination thereof.

[0272] In Formula 1, a1 to a5 respectively indicate the number of R₁ to the number of R₅. When a1 is 2 or more, two or more of R₁ may be identical to or different from each other, when a2 is 2 or more, two or more of R₂ may be identical to or different from each other, when a3 is 2 or more, two or more of R₃ may be identical to or different from each other, when a4 is 2 or more, two or more of R₄ may be identical to or different from each other, and when a5 is 2 or more, two or more of R₅ may be identical to or different from each other.

[0273] In an embodiment, Ar₁ may be:

[0274] a group represented by Formula 1A; or

[0275] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a

cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C₁-C₁₀ alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuran group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuran group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, an azadibenzofuran group, an azadibenzothiophenyl group, an azafluorenyl group, or an azadibenzosilolyl group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C₁-C₁₀ alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuran group, a benzothiophenyl group, a benzothiazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuran group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, —O(Q₃₁), —S(Q₃₁), —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —P(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), —P(=O)(Q₃₁)(Q₃₂), or any combination thereof, and

[0276] Q₃₁ to Q₃₃ may each independently be: hydrogen; deuterium; —F; —Cl; —Br; —I; a hydroxyl group; a cyano group; a nitro group; a C₁-C₆₀ alkyl group; a C₂-C₆₀ alkenyl group; a C₂-C₆₀ alkynyl group; a C₁-C₆₀ alkoxy group; or a C₅-C₆₀ carbocyclic group or a C₁-C₆₀ heterocyclic group, each unsubstituted or

substituted with deuterium, —F, a cyano group, a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a biphenyl group, or any combination thereof.

[0277] In an embodiment, Ar₁ may be:


[0278] a group represented by Formula 1A; or

[0279] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C₁-C₁₀ alkylphenyl group, or a naphthyl group, each unsubstituted or substituted with deuterium, —CD₃, —CD₂H, —CDH₂, a C₁-C₂₀ alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C₁-C₁₀ alkylphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), or any combination thereof, and

[0280] Q₃₁ to Q₃₃ may each independently be: hydrogen; deuterium; a C₁-C₆₀ alkyl group; a C₂-C₆₀ alkenyl group; a C₂-C₆₀ alkynyl group; or a C₅-C₆₀ carbocyclic group unsubstituted or substituted with deuterium, a C₁-C₆₀ alkyl group, a phenyl group, a biphenyl group, or any combination thereof.

[0281] In an embodiment, Ar₁ may be a group represented by Formula 1A.

[0282] In an embodiment, T₂₁ and T₂₂ may each independently be a group represented by Formula 1B:



[Formula 1B]

[0283] In Formula 1B,

[0284] R_{10a} may be the same as described herein, b1 and b2 may each independently be an integer from 1 to 4,


[0285] T₃ may be a single bond, *—O—**, *—S—**, *—N(R')—**, *—C(R')(R'')—**, or *—Si(R')(R'')—**,

[0286] R' and R'' may each independently be the same as described in connection with Q₁, and

[0287] * and ** each independently indicate a binding site to a neighboring atom.

[0288] In Formula 1B, b1 and b2 each independently indicate the number of R_{10a}. When b1 is 2 or more, two or more of R_{10a} may be identical to or different from each other with respect to (R_{10a})_{b1}, and when b2 is 2 or more, two or more of R_{10a} may be identical to or different from each other with respect to (R_{10a})_{b2}.

[0289] In an embodiment, the heterocyclic compound represented by Formula 1 may be represented by Formula 1-1:



[Formula 1-1]

[0290] In Formula 1-1,

[0291] T₁, T₂₁, T₂₂, and Ar₁ may each be the same as described herein,

[0292] X₁₁ may be C(R₁₁) or N, X₁₂ may be C(R₁₂) or N, X₁₃ may be C(R₁₃) or N, and X₁₄ may be C(R₁₄) or N,

[0293] X₂₁ may be C(R₂₁) or N, X₂₂ may be C(R₂₂) or N, and X₂₃ may be C(R₂₃) or N,

[0294] X₃₁ may be C(R₃₁) or N, X₃₂ may be C(R₃₂) or N, and X₃₃ may be C(R₃₃) or N,

[0295] X₄₁ may be C(R₄₁) or N, X₄₂ may be C(R₄₂) or N, and X₄₃ may be C(R₄₃) or N,

[0296] X₅₁ may be C(R₅₁) or N, X₅₂ may be C(R₅₂) or N, X₅₃ may be C(R₅₃) or N, and X₅₄ may be C(R₅₄) or N,

[0297] R₁₁ to R₁₄ may each independently be the same as described in connection with R₁,

[0298] R₂₁ to R₂₃ may each independently be the same as described in connection with R₂,

[0299] R₃₁ to R₃₃ may each independently be the same as described in connection with R₃,

[0300] R₄₁ to R₄₃ may each independently be the same as described in connection with R₄,

[0301] R₅₁ to R₅₄ may each independently be the same as described in connection with R₅, and

[0302] two or more neighboring groups among R₁₁ to R₁₄, R₂₁ to R₂₃, R₃₁ to R₃₃, R₄₁ to R₄₃, R₅₁ to R₅₄, Z₁ to Z₄, and Ar₁ may optionally be bonded to each other to form a

[0303] C₃-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a}.

[0304] In Formula 1, unless defined otherwise, R_{10a} may be:

[0305] hydrogen, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, or a nitro group;

[0306] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₃-C₆₀ carbocyclic group, a C₁-C₆₀ heterocyclic group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), —P(=O)(Q₁₁)(Q₁₂), or any combination thereof;

[0307] a C₃-C₆₀ carbocyclic group, a C₁-C₆₀ heterocyclic group, a C₆-C₆₀ aryloxy group, or a C₆-C₆₀ arylthio group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₆₀ carbocyclic group, a C₁-C₆₀ heterocyclic

clic group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), —P(=O)(Q₂₁)(Q₂₂), or any combination thereof; or

[0308] —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), or —P(=O)(Q₃₁)(Q₃₂).

[0309] In Formula 1, unless defined otherwise, Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ may each independently be: hydrogen; deuterium; —F; —Cl; —Br; —I; a hydroxyl group; a cyano group; a nitro group; a C₁-C₆₀ alkyl group; a C₂-C₆₀ alkenyl group; a C₂-C₆₀ alkynyl group; a C₁-C₆₀ alkoxy group; or a C₅-C₆₀ carbocyclic group or a C₁-C₆₀ heterocyclic group, each unsubstituted or substituted with deuterium, —F, a cyano group, a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a biphenyl group, or any combination thereof.

[0310] The heterocyclic compound may include an electron donor moiety including nitrogen, an electron acceptor moiety including boron, and a spiro core atom, wherein the spiro core atom may be bonded to the electron donor moiety via a first bond and a second bond, and the spiro core atom may be bonded to the electron acceptor moiety via a third bond and a fourth bond, the first bond, the second bond, the third bond, and the fourth bond may each be a single bond, and the heterocyclic compound may satisfy at least one of Conditions 1 to 3 as described herein.


[0311] In thermally activated delayed fluorescence (TADF), slow reverse intersystem crossing (RISC) as a speed-determining process may slow down the entire luminescence system. To achieve high-speed RISC, spatial separation of a highest occupied molecular orbital (HOMO) and a lowest unoccupied molecular orbital (LUMO) may be implemented, and spin-orbit coupling (SOC) may be strengthened. SOC may be strengthened through the heavy atom effect.

[0312] According to embodiments, spatial separation of the electron donor moiety and the electron acceptor moiety may be achieved within the molecule, and the electron donor moiety and the electron acceptor moiety may be orthogonal to each other via the spiro core atom. Accordingly, a highest occupied molecular orbital (HOMO) and a lowest unoccupied molecular orbital (LUMO) may be separated to generate TADF, and internal quantum efficiency may be improved due to high-speed RISC. In an embodiment, C, Si, Ge, and the like may be used as examples of the spiro core atom. In an embodiment, SOC may be strengthened due to the heavy atom effect, thereby accelerating RISC. In an embodiment, due to excellent high-temperature durability, thermal decomposition may not readily occur even under high-temperature conditions, thereby contributing to long lifespan of a device.

[0313] In an embodiment, when Conditions 1 to 3 as described herein are satisfied, the heterocyclic compound may include at least one bulky insulating site in the molecule, and unfavorable transfers, such as Dexter energy transfer (DET), may be suppressed.

[0314] Accordingly, by using the heterocyclic compound, an electronic device (e.g., an organic light-emitting device) having reduced driving voltage, improved color purity and efficiency, and increased lifespan may be implemented.

[Descriptions of Formulae 2, 3, 3-1 to 3-5, 502, and 503]



[0315] In Formula 2, L₅₁ to L₅₃ may each independently be a single bond, a C₃-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{10a}, or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a}.

[0316] In Formula 2, b51 to b53 respectively indicate the number of L₅₁ to L₅₃, and b51 to b53 may each independently be an integer from 1 to 5. When b51 is 2 or more, two or more of L₅₁ may be identical to or different from each other, when b52 is 2 or more, two or more of L₅₂ may be identical to or different from each other, and when b53 is 2 or more, two or more of L₅₃ may be identical to or different from each other. For example, b51 to b53 may each independently be 1 or 2.

[0317] In an embodiment, in Formula 2, L₅₁ to L₅₃ may each independently be:

[0318] a single bond; or

[0319] a benzene group, a naphthalene group, an anthracene group, a phenanthrene group, a triphenylene group, a pyrene group, a chrysene group, a cyclopentadiene group, a furan group, a thiophene group, a silole group, an indene group, a fluorene group, an indole group, a carbazole group, a benzofuran group, a dibenzofuran group, a benzothiophene group, a dibenzothiophene group, a benzosilole group, a dibenzosilole group, an azafluorene group, an azacarbazole group, an azadibenzofuran group, an azadibenzothiophene group, an azadibenzosilole group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a phenanthroline group, a pyrrole group, a pyrazole group, an imidazole group, a triazole group, an oxazole group, an isoxazole group, a thiazole group, an isothiazole group, an oxadiazole group, a thiadiazole group, a benzopyrazole group, a benzimidazole group, a benzoxazole group, a benzothiazole group, a benzoxadiazole group, a benzothiadiazole group, a dibenzooxazacilline group, a dibenzothiacilline group, a dibenzodihydroazacilline group, a dibenzodihydrodiacilline group, a dibenzodihydrocilline group, a dibenzodioxane group, a dibenzooxathiene group, a dibenzooxazine group, a dibenzopyran group, a dibenzodithiine group, a dibenzothiazine group, a dibenzothiopyran group, a dibenzocyclohexadiene group, a dibenzodihydropyridine group, or a dibenzodihydropyrazine group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a

phenylcarbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a dimethyldibenzosilolyl group, a diphenyldibenzosilolyl group, $-\text{O}(\text{Q}_{31})$, $-\text{S}(\text{Q}_{31})$, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{P}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, or any combination thereof, and

[0320] Q_{31} to Q_{33} may each independently be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a pyridazinyl group, a pyrazinyl group, or a triazinyl group.

[0321] In an embodiment, in Formula 2, a bond between L_{51} and R_{51} , a bond between L_{52} and R_{52} , a bond between L_{53} and R_{53} , a bond between two or more of L_{51} , a bond between two or more of L_{52} , a bond between two or more of L_{53} , a bond between L_{51} and carbon between X_{54} and X_{55} , a bond between L_{52} and carbon between X_{54} and X_{56} , and a bond between L_{53} and carbon between X_{55} and X_{56} may each be a “carbon-carbon single bond.”

[0322] In Formula 2, X_{54} may be N or C(R_{54}), X_{55} may be N or C(R_{55}), and X_{56} may be N or C(R_{56}), wherein at least one of X_{54} to X_{56} may each be N. R_{54} to R_{56} may each be the same as described herein. In an embodiment, two or three of X_{54} to X_{56} may each be N.

[0323] In Formula 2, R_{51} to R_{56} may each independently be hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{60} alkyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkenyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkynyl group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkoxy group unsubstituted or substituted with at least one R_{10a} , a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} aryloxy group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} arylthio group unsubstituted or substituted with at least one R_{10a} , a C_7 - C_{60} arylalkyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} heteroarylalkyl group unsubstituted or substituted with at least one R_{10a} , $-\text{C}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})_2(\text{Q}_1)$, or $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$. Q_1 to Q_3 may each be the same as described herein.

[0324] In an embodiment, in Formula 2, R_{51} to R_{56} may each independently be:

[0325] hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, or a C_1 - C_{20} alkoxy group;

[0326] a C_1 - C_{20} alkyl group or a C_1 - C_{20} alkoxy group, each substituted with deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, $-\text{CD}_3$, $-\text{CD}_2\text{H}$, $-\text{CDH}_2$, $-\text{CF}_3$, $-\text{CF}_2\text{H}$, $-\text{CFH}_2$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{10} alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or any combination thereof;

[0327] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a


cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azafluorenyl group, an azadibenzosilolyl group, or a group represented by Formula 91, each unsubstituted or substituted with deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, $-\text{CD}_3$, $-\text{CD}_2\text{H}$, $-\text{CDH}_2$, $-\text{CF}_3$, $-\text{CF}_2\text{H}$, $-\text{CFH}_2$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, $-\text{O}(\text{Q}_{31})$, $-\text{S}(\text{Q}_{31})$, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{P}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, or any combination thereof; or

[0328] $-\text{C}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})_2(\text{Q}_1)$, or $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, and

[0329] Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be:

[0330] CH_3 , $-\text{CD}_3$, $-\text{CD}_2\text{H}$, $-\text{CDH}_2$, $-\text{CH}_2\text{CH}_3$, $-\text{CH}_2\text{CD}_3$, $-\text{CH}_2\text{CD}_2\text{H}$, $-\text{CH}_2\text{CDH}_2$, $-\text{CHDCCH}_3$, $-\text{CHDCD}_2\text{H}$, $-\text{CHDCDH}_2$, $-\text{CHDCD}_3$, $-\text{CD}_2\text{CD}_3$, $-\text{CD}_2\text{CD}_2\text{H}$, or $-\text{CD}_2\text{CDH}_2$; or

[0331] an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyridazinyl group, a pyrazinyl group, or a triazinyl group, each unsubstituted or substituted with deuterium, a C_1 - C_{10} alkyl group, a phenyl group, a biphenyl group, a pyridinyl group, a pyrimidinyl group, a pyridazinyl group, a pyrazinyl group, a triazinyl group, or any combination thereof;



[Formula 91]

[0332] In Formula 91,

[0333] ring CY_{91} and ring CY_{92} may each independently be a C_5 - C_{30} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{30} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,

[0334] X_{91} may be a single bond, O, S, N(R_{91}), B(R_{91}), C(R_{91a})(R_{91b}), or Si(R_{91a})(R_{91b}),

[0335] R_{91} , R_{91a} , and R_{91b} may respectively be the same as described in connection with R_{82} , R_{82a} , and R_{82b} , as described herein,

[0336] R_{10a} may be the same as described herein, and

[0337] * indicates a binding site to a neighboring atom.

[0338] In an embodiment, in Formula 91,

[0339] ring CY_{91} and ring CY_{92} may each independently be a benzene group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, or a triazine group, each unsubstituted or substituted with at least one R_{10a} , and

[0340] R_{91} , R_{91a} , and R_{91b} may each independently be:

[0341] hydrogen or a C_1 - C_{10} alkyl group; or

[0342] a phenyl group, a pyridinyl group, a pyrimidinyl group, a pyridazinyl group, a pyrazinyl group, or a triazinyl group, each unsubstituted or substituted with deuterium, a C_1 - C_{10} alkyl group, a phenyl group, a biphenyl group, a pyridinyl group, a pyrimidinyl group, a pyridazinyl group, a pyrazinyl group, a triazinyl group, or any combination thereof.

[0343] In an embodiment, in Formula 2, a group represented by $*(\text{L}_{51})_{b51}\text{-R}_{51}$ and a group represented by $*(\text{L}_{52})_{b52}\text{-R}_{52}$ may each not be a phenyl group.

[0344] In an embodiment, in Formula 2, a group represented by $*(\text{L}_{51})_{b51}\text{-R}_{51}$ and a group represented by $*(\text{L}_{52})_{b52}\text{-R}_{52}$ may be identical to each other.

[0345] In embodiments, in Formula 2, a group represented by $*(\text{L}_{51})_{b51}\text{-R}_{51}$ and a group represented by $*(\text{L}_{52})_{b52}\text{-R}_{52}$ may be different from each other.

[0346] In embodiments, in Formula 2, R_{51} and R_{52} may each independently be 1, 2, or 3; and L_{51} and L_{52} may each independently be a benzene group, a pyridine group, a pyrimidine group, a pyridazine group, a pyrazine group, or a triazine group, each unsubstituted or substituted with at least one R_{10a} .

[0347] In an embodiment, in Formula 2, R_{51} and R_{52} may each independently be a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} aryloxy group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} arylthio group unsubstituted or substituted with at least one R_{10a} , $-\text{C}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, or $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, and


[0348] Q_1 to Q_3 may each independently be a C_8 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group, each unsubstituted or substituted with deuterium, $-\text{F}$, a cyano group, a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a biphenyl group, or any combination thereof.

[0349] In an embodiment, in Formula 2,










[0350] a group represented by $*(\text{L}_{51})_{b51}\text{-R}_{51}$ may be a group represented by one of Formulae CY51-1 to CY51-26, and/or

[0351] a group represented by $*(\text{L}_{52})_{b52}\text{-R}_{52}$ may be a group represented by one of Formulae CY52-1 to CY52-26, and/or

[0352] a group represented by $*(\text{L}_{53})_{b53}\text{-R}_{53}$ may be a group represented by one of Formulae CY53-1 to CY53-27, $-\text{C}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, or $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$:



-continued



CY51-6

CY51-7

CY51-8

CY51-9

CY51-10







CY51-11

CY51-12

CY51-13

CY51-14

-continued



CY51-15

CY51-16







CY51-17

CY51-18

CY51-19

CY51-20

-continued



CY51-21

CY51-22










CY51-23

CY51-24

CY51-25

CY51-26

-continued



CY52-1

CY52-2

CY52-3

CY52-4

CY52-5








CY52-6

CY52-7

CY52-8

CY52-9

-continued



CY52-10

CY52-11

CY52-12







CY52-13

CY52-14

CY52-15

CY52-16

-continued



CY52-17

CY52-18








CY52-19

CY52-20

CY52-21

CY52-22

-continued



CY52-23

CY52-24

CY52-25









CY52-26

CY53-1

CY53-2

CY53-3

-continued



CY53-4

CY53-5

CY53-6

CY53-7









CY53-8

CY53-9

CY53-10

CY53-11

-continued



CY53-12

CY53-13

CY53-14

CY53-15









CY53-16

CY53-17

CY53-18

CY53-19

-continued



CY53-20

CY53-21

CY53-22

CY53-23

CY53-24

CY53-25

CY53-26

CY53-27

[0353] In Formulae CY51-1 to CY51-26, CY52-1 to CY52-26, and CY53-1 to CY53-27,

[0354] Y_{63} may be a single bond, O, S, N(R_{63}), B(R_{63}), C(R_{63a})(R_{63a}), or Si(R_{63a})(R_{63a}),


[0355] Y_{64} may be a single bond, O, S, N(R_{64}), B(R_{64}), C(R_{64a})(R_{64b}), or Si(R_{64a})(R_{64b}),

[0356] Y_{67} may be a single bond, O, S, N(R_{67}), B(R_{67}), C(R_{67a})(R_{67b}), or Si(R_{67a})(R_{67b}),

- [0357] Y_{68} may be a single bond, O, S, N(R_{68}), B(R_{68}), C(R_{68a})(R_{68b}), or Si(R_{68a})(R_{68b}),
- [0358] Y_{63} and Y_{64} in Formulae CY51-16 and CY51-17 may each not be a single bond at the same time,
- [0359] Y_{67} and Y_{68} in Formulae CY52-16 and CY52-17 may each not be a single bond at the same time,
- [0360] R_{51a} to R_{51e} , R_{61} to R_{64} , R_{63a} , R_{63b} , R_{64a} , and R_{64b} may each independently be the same as described in connection with R_{51} , except that R_{51a} to R_{51e} may each not be hydrogen,
- [0361] R_{52a} to R_{52e} , R_{65} to R_{68} , R_{67a} , R_{67b} , R_{68a} , and R_{68b} may each independently be the same as described in connection with R_{52} , except that R_{52a} to R_{52e} may each not be hydrogen,
- [0362] R_{53a} to R_{53e} , R_{69a} , and R_{69b} may each independently be the same as described in connection with R_{53} , except that R_{53a} to R_{53e} may each not be hydrogen, and
- [0363] * indicates a binding site to a neighboring atom.
- [0364] In an embodiment,
- [0365] in Formulae CY51-1 to CY51-26 and CY52-1 to 52-26, R_{51a} to R_{51e} and R_{52a} to R_{52e} may each independently be:
- [0366] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, an azadibenzofuranlyl group, an azadibenzothiophenyl group, an azafluorenyl group, an azadibenzosilolyl group, or a group represented by Formula 91, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkoxy group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophe-

- nyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, or any combination thereof; or
- [0367] —C(Q_1)(Q_2)(Q_3) or —Si(Q_1)(Q_2)(Q_3),
- [0368] Q_1 to Q_3 may each independently be a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyridazinyl group, a pyrazinyl group, or a triazinyl group, each unsubstituted or substituted with deuterium, a C_1 - C_{10} alkyl group, a phenyl group, a biphenyl group, a pyridinyl group, a pyrimidinyl group, a pyridazinyl group, a pyrazinyl group, a triazinyl group, or any combination thereof,
- [0369] in Formulae CY51-16 and CY51-17, Y_{63} may be O or S, and Y_{64} may be Si(R_{64a})(R_{64b}); or Y_{63} may be Si(R_{63a})(R_{63b}), and Y_{64} may be O or S, and
- [0370] in Formulae CY52-16 and CY52-17, Y_{67} may be O or S, and Y_{68} may be Si(R_{68a})(R_{68b}); or Y_{67} may be Si(R_{67a})(R_{67b}), and Y_{68} may be O or S.

[Formula 3]




[0371] In Formula 3, ring CY₇₁ and ring CY₇₂ may each independently be a π electron-rich C_3 - C_{60} cyclic group or a pyridine group.

[0372] In Formula 3, X₇₁ may be: a single bond; or a linking group including O, S, N, B, C, Si, or any combination thereof.


[0373] In Formula 3, * indicates a binding site to any atom included in a remaining part of the third compound other than the group represented by Formula 3.

[Formula 3-1]




-continued


[Formula 3-2]



[Formula 3-3]



[Formula 3-4]



[Formula 3-5]

[0374] In Formulae 3-1 to 3-5, ring CY₇₁ to ring CY₇₄ may each independently be a IT electron-rich C₃-C₆₀ cyclic group or a pyridine group.

[0375] In Formulae 3-1 to 3-5, X₈₂ may be a single bond, O, S, N—[(L₈₂)₆₈₂-R₈₂], C(R_{82a})(R_{82b}), or Si(R_{82a})(R_{82b}).

[0376] In Formulae 3-1 to 3-5, X₈₃ may be a single bond, O, S, N—[(L₈₃)₆₈₃-R₈₃], C(R_{83a})(R_{83b}), or Si(R_{83a})(R_{83b}).

[0377] In Formulae 3-1 to 3-5, X₈₄ may be O, S, N—[(L₈₄)₆₈₄-R₈₄], C(R_{84a})(R_{84b}), or Si(R_{84a})(R_{84b}).

[0378] In Formulae 3-1 to 3-5, X₈₅ may be C or Si.

[0379] In Formulae 3-1 to 3-5, L₈₁ to L₈₅ may each independently be a single bond, *—C(Q₄)(Q₅)—**, *—Si(Q₄)(Q₅)—**, a π electron-rich C₃-C₆₀ cyclic group unsubstituted or substituted with at least one R_{10a}, or a pyridine group unsubstituted or substituted with at least one R_{10a}.

[0380] In Formulae 3-1 to 3-5, Q₄ and Q₅ may each independently be the same as described in connection with Q₁.

[0381] In Formulae 3-1 to 3-5, b81 to b85 may each independently be an integer from 1 to 5.

[0382] In Formulae 3-1 to 3-5, R₇₁ to R₇₄, R₈₁ to R₈₅, R_{82a}, R_{82b}, R_{83a}, R_{83b}, R_{84a}, and R_{84b} may each be the same as described herein.

[0383] In Formulae 3-1 to 3-5, a71 to a74 respectively indicate the number of R₇₁ to the number of R₇₄, and a71 to a74 may each independently be an integer from 0 to 20. When a71 is 2 or more, two or more of R₇₁ may be identical to or different from each other, when a72 is 2 or more, two or more of R₇₂ may be identical to or different from each other, when a73 is 2 or more, two or more of R₇₃ may be identical to or different from each other, and when a74 is 2 or more, two or more of R₇₄ may be identical to or different from each other. In an embodiment, a71 to a74 may each independently be an integer from 0 to 8.

[0384] In Formulae 3-1 to 3-5, R_{10a} may be the same as described herein.

[0385] In an embodiment, in Formulae 3-1 to 3-5, L₈₁ to L₈₅ may each independently be:

[0386] a single bond; or


[0387] *—C(Q₄)(Q₅)—** or *—Si(Q₄)(Q₅)—**, or

[0388] a benzene group, a naphthalene group, an anthracene group, a phenanthrene group, a triphenylene group, a pyrene group, a chrysene group, a cyclopentadiene group, a furan group, a thiophene group, a silole group, an indene group, a fluorene group, an indole group, a carbazole group, a benzofuran group, a dibenzofuran group, a benzothiophene group, a dibenzothiophene group, a benzosilole group, a dibenzosilole group, an azafluorene group, an azacarbazole group, an azadibenzofuran group, an azadibenzothiophene group, an azadibenzosilole group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a phenanthroline group, a pyrrole group, a pyrazole group, an imidazole group, a triazole group, an oxazole group, an isoxazole group, a thiazole group, an isothiazole group, an oxadiazole group, a thiadiazole group, a benzopyrazole group, a benzimidazole group, a benzoxazole group, a benzothiazole group, a benzoxadiazole group, or a benzothiadiazole group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a dimethyldibenzosilolyl group, a diphenyldibenzosilolyl group, —O(Q₃₁), —S(Q₃₁), —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —P(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), —P(=O)(Q₃₁)(Q₃₂), or any combination thereof, and

[0389] Q₄, Q₅, and Q₃₁ to Q₃₃ may each independently be hydrogen, deuterium, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a


terphenyl group, a pyridinyl group, a pyrimidinyl group, a pyridazinyl group, a pyrazinyl group, or a triazinyl group.

[0390] In embodiments, in Formulae 3-1 and 3-2, a group represented by




may be a group represented by one of Formulae CY71-1(1) to CY71-1(8), and/or

[0391] in Formulae 3-1 and 3-3, a group represented by




may be a group represented by one of Formulae CY71-2(1) to CY71-2(8), and/or

[0392] in Formulae 3-2 and 3-4, a group represented by




may be a group represented by one of Formulae CY71-3(1) to CY71-3(32), and/or

[0393] in Formulae 3-3 to 3-5, a group represented by




may be a group represented by one of Formulae CY71-4(1) to CY71-4(32), and/or

[0394] in Formula 3-5, a group represented by




represented by one of Formulae CY71-5(1) to CY71-5(8):


CY71-1(1)




CY71-1(2)




CY71-1(3)




CY71-1(4)




CY71-1(5)




CY71-1(6)




CY71-1(7)





CY71-1(8)





-continued





CY71-3(1)





CY71-3(3)





CY71-3(4)





CY71-3(5)





CY71-3(6)




CY71-3(7)




CY71-3(8)




-continued




-continued




-continued




CY71-3(27)




CY71-3(28)




CY71-3(29)




CY71-3(30)




CY71-3(31)



CY71-3(32)




CY71-4(1)




CY71-4(2)


-continued




CY71-4(3)




CY71-4(4)




CY71-4(5)




CY71-4(6)



CY71-4(7)




CY71-4(8)




CY71-4(9)


-continued



-continued



-continued



-continued

CY71-4(25)

CY71-4(26)


CY71-4(27)

CY71-4(28)

CY71-4(29)

CY71-4(30)

CY71-4(31)



CY71-4(32)

CY71-5(1)

CY71-5(2)

CY71-5(3)


CY71-5(4)

CY71-5(5)

CY71-5(6)

CY71-5(7)

-continued



CY71-5(8)

[0395] In Formulae CY71-1(1) to CY71-1(8), CY71-2(1) to CY71-2(8), CY71-3(1) to CY71-3(32), CY71-4(1) to CY71-4(32), and CY71-5(1) to CY71-5(8),

[0396] X_{82} to X_{85} , L_{81} , b_{81} , R_{81} , and R_{85} may each be the same as described herein,

[0397] X_{86} may be a single bond, O, S, N(R_{86}), B(R_{86}), C(R_{86a})(R_{86b}), or Si(R_{86a})(R_{86b}),

[0398] X_{87} may be a single bond, O, S, N(R_{87}), B(R_{87}), C(R_{87a})(R_{87b}), or Si(R_{87a})(R_{87b}),


[0399] in Formulae CY71-1(1) to CY71-1(8) and CY71-4(1) to CY71-4(32), X_{86} and X_{87} may not each be a single bond at the same time,

[0400] X_{88} may be a single bond, O, S, N(R_{88}), B(R_{88}), C(R_{88a})(R_{88b}), or Si(R_{88a})(R_{88b}),


[0401] X_{89} may be a single bond, O, S, N(R_{89}), B(R_{89}), C(R_{89a})(R_{89b}), or Si(R_{89a})(R_{89b}),

[0402] in Formulae CY71-2(1) to CY71-2(8), CY71-3(1) to CY71-3(32), and CY71-5(1) to CY71-5(8), X_{88} and X_{89} may not each be a single bond at the same time, and

[0403] R_{86} to R_{89} , R_{86a} , R_{86b} , R_{87a} , R_{87b} , R_{88a} , R_{88b} , R_{89a} , and R_{89b} may each independently be the same as described in connection with R_{81} .



[Formula 502]



[Formula 503]

[0404] In Formulae 502 and 503, ring A_{501} to ring A_{504} may each independently be a C_3 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group.

[0405] In Formulae 502 and 503, Y_{505} may be O, S, N(R_{505}), B(R_{505}), C(R_{505a})(R_{505b}), or Si(R_{505a})(R_{505b}).

[0406] In Formulae 502 and 503, Y_{506} may be O, S, N(R_{506}), B(R_{506}), C(R_{506a})(R_{506b}), or Si(R_{506a})(R_{506b}).

[0407] In Formulae 502 and 503, Y_{507} may be O, S, N(R_{507}), B(R_{507}), C(R_{507a})(R_{507b}), or Si(R_{507a})(R_{507b}).

[0408] In Formulae 502 and 503, Y_{508} may be O, S, N(R_{508}), B(R_{508}), C(R_{508a})(R_{508b}), or Si(R_{508a})(R_{508b}).

[0409] In Formulae 502 and 503, Y_{51} and Y_{52} may each independently be B, P(=O), or S(=O).

[0410] In Formulae 502 and 503, R_{500a} , R_{500b} , R_{501} to R_{508} , R_{505a} , R_{505b} , R_{506a} , R_{506b} , R_{507a} , R_{507b} , R_{508a} , and R_{508b} may each be the same as described herein.

[0411] In Formulae 502 and 503, a_{501} to a_{504} respectively indicate the number of R_{501} to the number of R_{504} ; and a_{501} to a_{504} may each independently be an integer from 0 to 20. When a_{501} is 2 or more, two or more of R_{501} may be identical to or different from each other, when a_{502} is 2 or more, two or more of R_{502} may be identical to or different from each other, when a_{503} is 2 or more, two or more of R_{503} may be identical to or different from each other, and when a_{504} is 2 or more, two or more of R_{504} may be identical to or different from each other. In an embodiment, a_{501} to a_{504} may each independently be an integer from 0 to 8.

[0412] In the specification, R_{51} to R_{56} , R_{71} to R_{74} , R_{81} to R_{85} , R_{82a} , R_{82b} , R_{83a} , R_{83b} , R_{84a} , R_{84b} , R_{500a} , R_{500b} , R_{501} to R_{508} , R_{505a} , R_{505b} , R_{506a} , R_{506b} , R_{507a} , R_{507b} , R_{508a} , and R_{508b} may each independently be hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{60} alkyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkenyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkynyl group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkoxy group unsubstituted or substituted with at least one R_{10a} , a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} aryloxy group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} arylthio group unsubstituted or substituted with at least one R_{10a} , a C_7 - C_{60} arylalkyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} heteroarylalkyl group unsubstituted or substituted with at least one R_{10a} , —C(Q_1)(Q_2)(Q_3), —Si(Q_1)(Q_2)(Q_3), —N(Q_1)(Q_2), —B(Q_1)(Q_2), —C(=O)(Q_1), —S(=O)₂(Q_1), or —P(=O)(Q_1)(Q_2). Q_1 to Q_3 may each be the same as described herein.

[0413] In an embodiment, R_{51} to R_{56} , R_{71} to R_{74} , R_{81} to R_{85} , R_{82a} , R_{82b} , R_{83a} , R_{83b} , R_{84a} , R_{84b} , R_{500a} , R_{500b} , R_{501} to R_{508} , R_{505a} , R_{505b} , R_{506a} , R_{506b} , R_{507a} , R_{507b} , R_{508a} , and R_{508b} in Formulae 2, 3-1 to 3-5, 502, and 503, and R_{10a} may each independently be:

[0414] hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, or a C_1 - C_{20} alkoxy group;

[0415] a C_1 - C_{20} alkyl group or a C_1 - C_{20} alkoxy group, each substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{10} alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or any combination thereof;

[0416] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl

group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, a quinoxaliny group, a quinazoliny group, a cinnoliny group, a carbazolyl group, a phenanthroliny group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azafluorenyl group, an azadibenzosilolyl group, or a group represented by Formula 91, each unsubstituted or substituted with deuterium, $-F$, $-Cl$, $-Br$, $-I$, $-CD_3$, $-CD_2H$, $-CDH_2$, $-CF_3$, $-CF_2H$, $-CFH_2$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, a quinoxaliny group, a quinazoliny group, a cinnoliny group, a carbazolyl group, a phenanthroliny group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, $-O(Q_{31})$, $-S(Q_{31})$, $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{31})(Q_{32})$, $-B(Q_{31})(Q_{32})$, $-P(Q_{31})(Q_{32})$, $-C(=O)(Q_{31})$, $-S(=O)_2(Q_{31})$, $-P(=O)(Q_{31})(Q_{32})$, or any combination thereof; or

[0417] $-C(Q_1)(Q_2)(Q_3)$, $-Si(Q_1)(Q_2)(Q_3)$, $-N(Q_1)(Q_2)$, $-B(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-S(=O)_2(Q_1)$, or $-P(=O)(Q_1)(Q_2)$, and

[0418] Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be:

[0419] $-CH_3$, $-CD_3$, $-CD_2H$, $-CDH_2$, $-CH_2CH_3$, $-CH_2CD_3$, $-CH_2CD_2H$, $-CH_2CDH_2$, $-CHDCD_3$, $-CHDCD_2H$, $-CHDCDH_2$, $-CHDCD_3$, $-CD_2CD_3$, $-CD_2CD_2H$, or $-CD_2CDH_2$; or


[0420] an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyridazinyl group, a pyrazinyl group, or a triazinyl group, each unsubstituted or substituted with deuterium, a C_1 - C_{10} alkyl group, a phenyl group, a biphenyl group, a pyridinyl group, a pyrimidinyl group, a pyridazinyl group, a pyrazinyl group, a triazinyl group, or any combination thereof.

[0421] In embodiments, R_{61} to R_{63} in Formula 1A, R_1 to R_5 in Formula 1, R_{51} to R_{56} , R_{71} to R_{74} , R_{81} to R_{85} , R_{82a} , R_{82b} , R_{83a} , R_{83b} , R_{84a} , R_{84b} , R_{500a} , R_{500b} , R_{501} to R_{508} , R_{505a} , R_{505b} , R_{506a} , R_{506b} , R_{507a} , R_{507b} , R_{508a} , and R_{508b} in Formulae 2, 3-1 to 3-5, 502, and 503, and R_{10a} may each independently be:


[0422] hydrogen, deuterium, $-F$, a cyano group, a nitro group, $-CH_3$, $-CD_3$, $-CD_2H$, $-CDH_2$, $-CF_3$, $-CF_2H$, or $-CFH_2$;

[0423] a group represented by one of Formulae 9-1 to 9-19; or

[0424] a group represented by one of Formulae 10-1 to 10-246, $-C(Q_1)(Q_2)(Q_3)$, $-Si(Q_1)(Q_2)(Q_3)$, or $-P(=O)(Q_1)(Q_2)$ (wherein Q_1 to Q_3 may each be the same as described herein).



-continued



9-9

9-10

9-11

9-12

9-13

9-14

9-15

9-16

9-17

9-18

9-19


10-1

10-2

10-3

10-4

-continued



10-5

10-6

10-7

10-8

10-9

10-10

10-11


10-12

10-13


10-14

10-15


-continued




10-16




10-17




10-18




10-19




10-20




10-21




10-22



10-23




10-24




10-25


-continued




10-26




10-27




10-28




10-29




10-30




10-31




10-32



10-33




10-34




10-35


-continued




-continued




-continued




10-55




10-56




10-57




10-58




10-59



10-60




10-61




10-62


-continued




10-63




10-64




10-65




10-66




10-67




10-68




10-69



10-70




10-71




10-72


-continued




10-73




10-74




10-75



10-76




10-77




10-78


-continued




10-79




10-80




10-81




10-82




10-83



10-84




10-85




10-86


-continued




10-87




10-88




10-89




10-90




10-91




10-92




10-93




10-94




10-95




10-96



10-97




10-98




10-99


-continued




10-100




10-101




10-102




10-103




10-104




10-105




10-106



10-107




10-108




10-109


-continued




10-110




10-111




10-112




10-113



10-114




10-115




10-116


-continued




10-117




10-118




10-119




10-120



10-121




10-122



10-123

-continued



10-124

10-125

10-126

10-127


10-128

10-129

10-130

10-131

-continued



10-132

10-133

10-134


10-135

10-136


10-137

10-138


-continued




10-139




10-140




10-141




10-142



10-143




10-144




10-145


-continued




10-146




10-147




10-148




10-149




10-150




10-151



10-152




10-153




10-154


-continued




10-155




10-156




10-157




10-158




10-159




10-160




10-161



10-162




10-163




10-164


-continued




10-165




10-166




10-167




10-168




10-169



10-170




10-171




10-172


-continued




10-173




10-174




10-175




10-176




10-177



10-178




10-179




10-180


-continued




10-181




10-182




10-183




10-184




10-185




10-186




10-187




10-188




10-189



10-190




10-191




10-192


-continued




10-193




10-194




10-195




10-196




10-197




10-198




10-199




10-200



10-201




10-202




10-203


-continued




10-204




10-205




10-206




10-207




10-208



10-209




10-210




10-211

-continued




10-212


-continued




10-219




10-213




10-220




10-214




10-221




10-215




10-222




10-216




10-223




10-217



10-224




10-218




10-225


-continued




10-226




10-227




10-228



10-229




10-230




10-231


-continued




10-232



10-233




10-234




10-235




10-236



10-237




10-238



10-239

-continued



10-240

10-241

10-242


10-243

10-244

10-245

10-246

-continued



2

3


4

[0425] In Formulae 9-1 to 9-19 and 10-1 to 10-246, * indicates a binding site to a neighboring atom, Ph represents a phenyl group, and TMS represents a trimethylsilyl group.


5

Examples of Compounds


[0426] In an embodiment, the heterocyclic compound may be one of Compounds 1 to 6:



1



-continued



[Description of FIG. 1]

[0427] FIG. 1 is a schematic cross-sectional view of a light-emitting device 10 according to an embodiment. The light-emitting device 10 may include a first electrode 110, an interlayer 130, and a second electrode 150.

[0428] Hereinafter, the structure of the light-emitting device 10 according to an embodiment and a method of manufacturing the light-emitting device 10 will be described with reference to FIG. 1.

[First Electrode 110]

[0429] In FIG. 1, a substrate may be further included under the first electrode 110 or on the second electrode 150. In an embodiment, the substrate may be a glass substrate or a plastic substrate. In embodiments, the substrate may be a flexible substrate, and may include plastics with excellent heat resistance and durability, such as polyimide, polyethylene terephthalate (PET), polycarbonate, polyethylene naphthalate, polyarylate (PAR), polyetherimide, or any combination thereof.

[0430] The first electrode 110 may be formed by, for example, depositing or sputtering a material for forming the first electrode 110 on the substrate. When the first electrode 110 is an anode, a material for forming the first electrode 110 may be a high-work function material that facilitates injection of holes.

[0431] The first electrode 110 may be a reflective electrode, a transfective electrode, or a transmissive electrode. In an embodiment, when the first electrode 110 is a transmissive electrode, a material for forming the first electrode 110 may include indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), zinc oxide (ZnO), or any combination thereof. In embodiments, when the first electrode 110 is a transfective electrode or a reflective electrode, a material for forming the first electrode 110 may include magnesium (Mg), silver (Ag), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), or any combination thereof.

[0432] The first electrode 110 may have a structure consisting of a single layer, or a structure including multiple layers. For example, the first electrode 110 may have a three-layer structure of ITO/Ag/ITO.

[Interlayer 130]

[0433] The interlayer 130 may be arranged on the first electrode 110. The interlayer 130 may include an emission layer.

[0434] The interlayer 130 may further include a hole transport region between the first electrode 110 and the emission layer, and an electron transport region between the emission layer and the second electrode 150.

[0435] The interlayer 130 may further include, in addition to various organic materials, a metal-containing compound such as an organometallic compound, an inorganic material such as a quantum dot, or the like.

[0436] In an embodiment, the interlayer 130 may include two or more emitting units stacked between the first electrode 110 and the second electrode 150, and at least one charge generation layer between adjacent units among the two or more emitting units. When the interlayer 130 includes the two or more emitting units and the at least one charge generation layer, the light-emitting device 10 may be a tandem light-emitting device.



[Hole Transport Region in Interlayer 130]

[0437] The hole transport region may have a structure consisting of a layer consisting of a single material, a structure consisting of a layer including different materials, or a structure including multiple layers including different materials.

[0438] The hole transport region may include a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or any combination thereof.

[0439] In embodiments, the hole transport region may have a multi-layer structure including a hole injection layer/hole transport layer structure, a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole injection layer/emission auxiliary layer structure, a hole transport layer/emission auxiliary layer structure, or a hole injection layer/hole transport layer/electron blocking layer structure, wherein the layers of each structure may be stacked from the first electrode 110 in its respective stated order, but the structure of the hole transport region is not limited thereto.

[0440] In embodiments, the hole transport region may include a compound represented by Formula 201, a compound represented by Formula 202, or any combination thereof:



[0441] In Formulae 201 and 202,

[0442] L₂₀₁ to L₂₀₄ may each independently be a C₃-C₆₀ carbocyclic group unsubstituted or substituted with at

least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,

[0443] L_{205} may be $^*-O-^*$, $^*-S-^*$, $^*-N(Q_{201})-^*$, a C_1 - C_{20} alkylene group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{20} alkenylene group unsubstituted or substituted with at least one R_{10a} , a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,

[0444] $xa1$ to $xa4$ may each independently be an integer from 0 to 5,

[0445] $xa5$ may be an integer from 1 to 10,


[0446] R_{201} to R_{204} and Q_{201} may each independently be a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,

[0447] R_{201} and R_{202} may optionally be linked to each other via a single bond, a C_1 - C_5 alkylene group unsubstituted or substituted with at least one R_{10a} , or a C_2 - C_5 alkenylene group unsubstituted or substituted with at least one R_{10a} , to form a C_8 - C_{60} polycyclic group (e.g., a carbazole group, etc.) unsubstituted or substituted with at least one R_{10a} (e.g., Compound HT16, etc.),

[0448] R_{203} and R_{204} may optionally be linked to each other via a single bond, a C_1 - C_5 alkylene group unsubstituted or substituted with at least one R_{10a} , or a C_2 - C_5 alkenylene group unsubstituted or substituted with at least one R_{10a} , to form a C_8 - C_{60} polycyclic group unsubstituted or substituted with at least one R_{10a} , and

[0449] $na1$ may be an integer from 1 to 4.

[0450] In an embodiment, the compound represented by Formula 201 and the compound represented by Formula 202 may each independently include at least one of groups represented by Formulae CY201 to CY217:




CY201

CY202


CY203

CY204


-continued




CY205




CY206




CY207




CY208



CY209




CY210



CY211




CY212



CY213


-continued




CY214



CY215



CY216



CY217

[0451] In Formulae CY201 to CY217, R_{10b} and R_{10c} may each independently be the same as described in connection with R_{10a} , ring CY201 to ring CY204 may each independently be a C_3 - C_{20} carbocyclic group or a C_1 - C_{20} heterocyclic group, and at least one hydrogen in Formulae CY201 to CY217 may be unsubstituted or substituted with R_{10a} .

[0452] In an embodiment, in Formulae CY201 to CY217, ring CY201 to ring CY204 may each independently be a benzene group, a naphthalene group, a phenanthrene group, or an anthracene group.

[0453] In embodiments, the compound represented by Formula 201 and the compound represented by Formula 202 may each independently include at least one of groups represented by Formulae CY201 to CY203.

[0454] In embodiments, the compound represented by Formula 201 may include at least one of groups represented by Formulae CY201 to CY203 and at least one of groups represented by Formulae CY204 to CY217.

[0455] In embodiments, in Formula 201, xa_1 may be 1, R_{201} may be a group represented by one of Formulae CY201 to CY203, xa_2 may be 0, and R_{202} may be a group represented by one of Formulae CY204 to CY207.


[0456] In embodiments, the compound represented by Formula 201 and the compound represented by Formula 202 may each not include groups represented by Formulae CY201 to CY203.

[0457] In embodiments, the compound represented by Formula 201 and the compound represented by Formula 202 may each not include groups represented by Formulae CY201 to CY203, and may each independently include at least one of groups represented by Formulae CY204 to CY217.


[0458] In embodiments, the compound represented by Formula 201 and the compound represented by Formula 202 may each not include groups represented by Formulae CY201 to CY217.

[0459] In an embodiment, the hole transport region may include: one of Compounds HT1 to HT46; m-MTDATA; TDATA; 2-TNATA; NPB(NPD); β -NPB; TPD; spiro-TPD; spiro-NPB; methylated NPB; TAPC; HMTDPD; 4,4',4"-tris (N-carbazolyl)triphenylamine (TCTA); polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA); poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate)(PEDOT/PSS); polyaniline/camphor sulfonic acid (PANI/CSA); polyaniline/poly(4-styrenesulfonate) (PANI/PSS); or any combination thereof.

HT1




HT2




-continued


HT3




HT4



HT5




HT6




-continued


HT7




HT8




HT9




HT10




-continued
HT11




HT12




HT13




HT14




HT15




HT16




-continued




-continued
HT21




HT22




HT23



HT24




HT25




-continued


HT26




HT27




HT28




HT29



HT30




HT31




-continued


HT32




HT33




HT34




HT35




HT36




HT37




-continued
HT38




HT39




HT40




HT41




HT42




HT43




-continued
HT44




HT45




HT46



m-MTDATA




TDATA





2-TNATA


-continued




NPB

 β -NPB


TPD




Spiro-TPD




Spiro-TPD



methylated NPB



TAPC



HMTDP

[0460] A thickness of the hole transport region may be in a range of about 50 Å to about 10,000 Å. For example, the thickness of the hole transport region may be in a range of about 100 Å to about 4,000 Å. When the hole transport region includes a hole injection layer, a hole transport layer, or any combination thereof, a thickness of the hole injection layer may be in a range of about 100 Å to about 9,000 Å, and a thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å. For example, the thickness of the hole injection layer may be in a range of about 100 Å to about 1,000 Å. For example, the thickness of the hole transport layer may be in a range of about 100 Å to about

1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within the ranges described above, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

[0461] The emission auxiliary layer may increase light-emission efficiency by compensating for an optical resonance distance according to a wavelength of light emitted by the emission layer, and the electron blocking layer may block the leakage of electrons from the emission layer to the hole transport region. Materials that may be included in the

hole transport region may be included in the emission auxiliary layer and the electron blocking layer.

[p-Dopant]

[0462] The hole transport region may further include, in addition to the materials described above, a charge-generation material for the improvement of conductive properties. The charge-generation material may be uniformly or non-uniformly dispersed in the hole transport region (e.g., in the form of a single layer consisting of a charge-generation material).


[0463] The charge-generation material may be, for example, a p-dopant.

[0464] For example, the p-dopant may have a lowest unoccupied molecular orbital (LUMO) energy level less than or equal to about -3.5 eV.

[0465] In an embodiment, the p-dopant may include a quinone derivative, a cyano group-containing compound, a compound including element EL1 and element EL2, or any combination thereof.

[0466] Examples of a quinone derivative may include TCNQ, F4-TCNQ, and the like.

[0467] Examples of a cyano group-containing compound may include HAT-CN, a compound represented by Formula 221, and the like:



[0468] In Formula 221,

[0469] R₂₂₁ to R₂₂₃ may each independently be a C₃-C₆₀ carbocyclic group unsubstituted or substituted with at least

one R_{10a} or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a}, and

[0470] at least one of R₂₂₁ to R₂₂₃ may each independently be a C₃-C₆₀ carbocyclic group or a C₁-C₆₀ heterocyclic group, each substituted with: a cyano group; —F; —Cl; —Br; —I; a C₁-C₂₀ alkyl group substituted with a cyano group, —F, —Cl, —Br, —I, or any combination thereof; or any combination thereof.

[0471] In the compound including element EL1 and element EL2, element EL1 may be a metal, a metalloid, or any combination thereof, and element EL2 may be a non-metal, a metalloid, or any combination thereof.

[0472] Examples of a metal may include: an alkali metal (e.g., lithium (Li), sodium (Na), potassium (K), rubidium (Rb), cesium (Cs), etc.); an alkaline earth metal (e.g., beryllium (Be), magnesium (Mg), calcium (Ca), strontium (Sr), barium (Ba), etc.); a transition metal (e.g., titanium (Ti), zirconium (Zr), hafnium (Hf), vanadium (V), niobium (Nb), tantalum (Ta), chromium (Cr), molybdenum (Mo), tungsten (W), manganese (Mn), technetium (Tc), rhenium (Re), iron (Fe), ruthenium (Ru), osmium (Os), cobalt (Co), rhodium (Rh), iridium (Ir), nickel (Ni), palladium (Pd), platinum (Pt), copper (Cu), silver (Ag), gold (Au), etc.); a post-transition metal (e.g., zinc (Zn), indium (In), tin (Sn), etc.); a lanthanide metal (e.g., lanthanum (La), cerium (Ce), praseodymium (Pr), neodymium (Nd), promethium (Pm), samarium (Sm), europium (Eu), gadolinium (Gd), terbium (Tb), dysprosium (Dy), holmium (Ho), erbium (Er), thulium (Tm), ytterbium (Yb), lutetium (Lu), etc.); and the like.

[0473] Examples of a metalloid may include silicon (Si), antimony (Sb), tellurium (Te), and the like.

[0474] Examples of a non-metal may include oxygen (O), a halogen (e.g., F, Cl, Br, I, etc.), and the like.

[0475] Examples of a compound including element EL1 and element EL2 may include a metal oxide, a metal halide (e.g., a metal fluoride, a metal chloride, a metal bromide, a metal iodide, etc.), a metalloid halide (e.g., a metalloid fluoride, a metalloid chloride, a metalloid bromide, a metalloid iodide, etc.), a metal telluride, or any combination thereof.

[0476] Examples of a metal oxide may include a tungsten oxide (e.g., WO, W₂O₃, WO₂, WO₃, W₂O₅, etc.), a vanadium oxide (e.g., VO, V₂O₃, VO₂, V₂O₅, etc.), a molybdenum oxide (e.g., MoO, Mo₂O₃, MoO₂, MoO₃, Mo₂O₅, etc.), a rhenium oxide (e.g., ReO₃, etc.), and the like.

[0477] Examples of a metal halide may include an alkali metal halide, an alkaline earth metal halide, a transition metal halide, a post-transition metal halide, a lanthanide metal halide, and the like.

[0478] Examples of an alkali metal halide may include LiF, NaF, KF, RbF, CsF, LiCl, NaCl, KCl, RbCl, CsCl, LiBr, NaBr, KBr, RbBr, CsBr, LiI, NaI, KI, RbI, CsI, and the like.

[0479] Examples of an alkaline earth metal halide may include BeF₂, MgF₂, CaF₂, SrF₂, BaF₂, BeCl₂, MgCl₂, CaCl₂, SrCl₂, BaCl₂, BeBr₂, MgBr₂, CaBr₂, SrBr₂, BaBr₂, BeI₂, MgI₂, CaI₂, SrI₂, BaI₂, and the like.

[0480] Examples of a transition metal halide may include a titanium halide (e.g., TiF₄, TiCl₄, TiBr₄, TiI₄, etc.), a zirconium halide (e.g., ZrF₄, ZrCl₄, ZrBr₄, ZrI₄, etc.), a hafnium halide (e.g., HfF₄, HfCl₄, HfBr₄, HfI₄, etc.), a vanadium halide (e.g., VF₃, VCl₃, VBr₃, VI₃, etc.), a niobium halide (e.g., NbF₃, NbCl₃, NbBr₃, NbI₃, etc.), a tantalum halide (e.g., TaF₃, TaCl₃, TaBr₃, TaI₃, etc.), a chromium halide (e.g., CrF₃, CrCl₃, CrBr₃, CrI₃, etc.), a

molybdenum halide (e.g., MoF₃, MoCl₃, MoBr₃, MoI₃, etc.), a tungsten halide (e.g., WF₃, WCl₃, WBr₃, WI₃, etc.), a manganese halide (e.g., MnF₂, MnCl₂, MnBr₂, MnI₂, etc.), a technetium halide (e.g., TcF₂, TcCl₂, TcBr₂, TcI₂, etc.), a rhenium halide (e.g., ReF₂, ReCl₂, ReBr₂, ReI₂, etc.), an iron halide (e.g., FeF₂, FeCl₂, FeBr₂, FeI₂, etc.), a ruthenium halide (e.g., RuF₂, RuCl₂, RuBr₂, RuI₂, etc.), an osmium halide (e.g., OsF₂, OsCl₂, OsBr₂, OsI₂, etc.), a cobalt halide (e.g., CoF₂, CoCl₂, CoBr₂, CoI₂, etc.), a rhodium halide (e.g., RhF₂, RhCl₂, RhBr₂, RhI₂, etc.), an iridium halide (e.g., IrF₂, IrCl₂, IrBr₂, IrI₂, etc.), a nickel halide (e.g., NiF₂, NiCl₂, NiBr₂, NiI₂, etc.), a palladium halide (e.g., PdF₂, PdCl₂, PdBr₂, PdI₂, etc.), a platinum halide (e.g., PtF₂, PtCl₂, PtBr₂, PtI₂, etc.), a copper halide (e.g., CuF, CuCl, CuBr, CuI, etc.), a silver halide (e.g., AgF, AgCl, AgBr, AgI, etc.), a gold halide (e.g., AuF, AuCl, AuBr, AuI, etc.), and the like.

[0481] Examples of a post-transition metal halide may include a zinc halide (e.g., ZnF₂, ZnCl₂, ZnBr₂, ZnI₂, etc.), an indium halide (e.g., InI₃, etc.), a tin halide (e.g., SmI₂, etc.), and the like.

[0482] Examples of a lanthanide metal halide may include YbF, YbF₂, YbF₃, SmF₃, YbCl, YbCl₂, YbCl₃, SmCl₃, YbBr, YbBr₂, YbBr₃, SmBr₃, YbI, YbI₂, YbI₃, SmI₃, and the like.

[0483] Examples of a metalloid halide may include an antimony halide (e.g., SbCl₃, etc.) and the like.

[0484] Examples of a metal telluride may include an alkali metal telluride (e.g., Li₂Te, Na₂Te, K₂Te, Rb₂Te, Cs₂Te, etc.), an alkaline earth metal telluride (e.g., BeTe, MgTe, CaTe, SrTe, BaTe, etc.), a transition metal telluride (e.g., TiTe₂, ZrTe₂, HfTe₂, V₂Te₃, Nb₂Te₃, Ta₂Te₃, Cr₂Te₃, Mo₂Te₃, W₂Te₃, MnTe, TcTe, ReTe, FeTe, RuTe, OsTe, CoTe, RhTe, IrTe, NiTe, PdTe, PtTe, Cu₂Te, CuTe, Ag₂Te, AgTe, Au₂Te, etc.), a post-transition metal telluride (e.g., ZnTe, etc.), a lanthanide metal telluride (e.g., LaTe, CeTe, PrTe, NdTe, PmTe, EuTe, GdTe, TbTe, DyTe, HoTe, ErTe, TmTe, YbTe, LuTe, etc.), and the like.

[Emission Layer in Interlayer 130]

[0485] When the light-emitting device 10 is a full-color light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and/or a blue emission layer, according to a subpixel. In an embodiment, the emission layer may have a stacked structure of two or more of a red emission layer, a green emission layer, and a blue emission layer, in which the two or more layers may contact each other or may be separated from each other to emit white light. In embodiments, the emission layer may include two or more of a red light-emitting material, a green light-emitting material, and a blue light-emitting material, in which the two or more materials may be mixed with each other in a single layer to emit white light.

[0486] In an embodiment, the emission layer may include a host and a dopant (or emitter). In embodiments, the emission layer may further include an auxiliary dopant that promotes energy transfer to a dopant (or emitter), in addition to the host and the dopant (or emitter). When the emission layer includes the dopant (or emitter) and the auxiliary dopant, the dopant (or emitter) and the auxiliary dopant may be different from each other.

[0487] The heterocyclic compound as described herein may serve as a dopant (or emitter), or may serve as an auxiliary dopant.

[0488] An amount (by weight) of the dopant (or emitter) in the emission layer may be in a range of about 0.01 parts by weight to about 15 parts by weight, based on 100 parts by weight of the host.

[0489] In an embodiment, the heterocyclic compound may be included in the emission layer. An amount (by weight) of the heterocyclic compound in the emission layer may be in a range of about 0.01 parts by weight to about 30 parts by weight, based on 100 parts by weight of the emission layer. For example, the amount of the heterocyclic compound in the emission layer may be in a range of about 0.1 parts by weight to about 20 parts by weight, based on 100 parts by weight of the emission layer. For example, the amount of the heterocyclic compound in the emission layer may be in a range of about 0.1 parts by weight to about 15 parts by weight, based on 100 parts by weight of the emission layer.


[0490] In embodiments, the emission layer may include a quantum dot.

[0491] In embodiments, the emission layer may include a delayed fluorescence material. The delayed fluorescence material may serve as a host or as a dopant in the emission layer.

[0492] A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å. For example, the thickness of the emission layer may be in a range of about 200 Å to about 600 Å. When the thickness of the emission layer is within any of the ranges described above, excellent luminescence characteristics may be obtained without a substantial increase in driving voltage. [Host]

[0493] In an embodiment, the host in the emission layer may include the second compound, the third compound, or any combination thereof.

[0494] In embodiments, the host may include a compound represented by Formula 301:



[0495] In Formula 301,

[0496] Ar₃₀₁ and L₃₀₁ may each independently be a C₃-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{10a}, or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a},

[0497] xb11 may be 1, 2, or 3,

[0498] xb1 may be an integer from 0 to 5,



[0499] R₃₀₁ may be hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₆₀ alkyl group unsubstituted or substituted with at least one R_{10a}, a C₂-C₆₀ alkenyl group unsubstituted or substituted with at least one R_{10a}, a C₂-C₆₀ alkynyl group unsubstituted or substituted with at least one R_{10a}, a C₁-C₆₀ alkoxy group unsubstituted or substituted with at least one R_{10a}, a C₃-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{10a}, a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a}, —Si(Q₃₀₁)(Q₃₀₂)(Q₃₀₃), —N(Q₃₀₁)(Q₃₀₂), —B(Q₃₀₁)(Q₃₀₂), —C(=O)(Q₃₀₁), —S(=O)₂(Q₃₀₁), or —P(=O)(Q₃₀₁)(Q₃₀₂),

[0500] xb21 may be an integer from 1 to 5, and

[0501] Q₃₀₁ to Q₃₀₃ may each independently be the same as described in connection with Q₁.

[0502] In an embodiment, in Formula 301, when xb11 is 2 or more, two or more of Ar₃₀₁ may be linked to each other via a single bond.

[0503] In embodiments, the host may include a compound represented by Formula 301-1, a compound represented by Formula 301-2, or any combination thereof:



[0504] In Formulae 301-1 and 301-2,

[0505] ring A₃₀₁ to ring A₃₀₄ may each independently be a C₅-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a},

[0506] X₃₀₁ may be O, S, N—[(L₃₀₄)_{xb4}-R₃₀₄], C(R₃₀₄)(R₃₀₅), or Si(R₃₀₄)(R₃₀₅),

[0507] xb22 and xb23 may each independently be 0, 1, or 2,

[0508] L₃₀₁, xb1, and R₃₀₁ may each be the same as described herein,


[0509] L₃₀₂ to L₃₀₄ may each independently be the same as described in connection with L₃₀₁,

[0510] xb2 to xb4 may each independently be the same as described in connection with xb1, and


[0511] R₃₀₂ to R₃₀₅ and R₃₁₁ to R₃₁₄ may each independently be the same as described in connection with R₃₀₁.

[0512] In embodiments, the host may include an alkali earth metal complex, a post-transition metal complex, or any combination thereof. For example, the host may include a Be complex (e.g., Compound H55), a Mg complex, a Zn complex, or any combination thereof.


[0513] In embodiments, the host may include one of Compounds H1 to H128, 9,10-di(2-naphthyl) anthracene (ADN), 2-methyl-9,10-bis(naphthalen-2-yl) anthracene (MADN); 9,10-di(2-naphthyl)-2-t-butyl-anthracene (TBADN), 4,4'-bis(N-carbazolyl)—1,1'-biphenyl (CBP), 1,3-di-9-carbazolylbenzene (mCP), 1,3,5-tri (carbazol-9-yl) benzene (TCP), or any combination thereof:




H1



H2




H3





H4

-continued





H5

H6





H7

H8





H9

H10




H11

H12




H13


H14




-continued




H15




H16




H17




H18




H19



H20




H21




H22

-continued


H23




H24




H25




H26



H27




H28




-continued


H29




H30




H31




H32




H33




H34




-continued
H35




H36




H37




H38



H39




H40





-continued

H41





H42

H43




H44

H45




-continued


H46




H47




H48




H49




H50




H51




H52




H53



H54




H55




-continued


H56




H57




H58




H59




H60




H61




H62




H63



H64




H65




-continued


H66




H67




H68




H69




H70




H71




H72




H73




H74




H75




-continued
H76




H77




H78




H79




H80




H81




H82




H83



H84




H85




-continued


H86




H87




H88




H89



H90




H91




-continued


H92




H93




H94




H95




H96




H97



H98




H99




-continued


H100




H101




H102




H103



H104




H105




-continued


H106




H107




H108




H109




H110




H111



H112




H113




-continued


H114




H115




H116



H117




H118




-continued


H119




H120




H121




H122



H123




H124




-continued


H125




H126



H127



H128



[0514] In an embodiment, the host may include a silicon-containing compound, a phosphine oxide-containing compound, or any combination thereof.

[0515] The host may have various modifications. For example, the host may include only one kind of compound, or may include two or more kinds of different compounds.


[Phosphorescent Dopant]

[0516] In an embodiment, the phosphorescent dopant may include at least one transition metal as a central metal.

[0517] The phosphorescent dopant may include a monodentate ligand, a bidentate ligand, a tridentate ligand, a tetradentate ligand, a pentadentate ligand, a hexadentate ligand, or any combination thereof.


[0518] The phosphorescent dopant may be electrically neutral.

[0519] In an embodiment, the phosphorescent dopant may include an organometallic compound represented by Formula 401:



[Formula 401]

[Formula 402]



[0520] In Formulae 401 and 402,

[0521] M may be a transition metal (e.g., iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), gold (Au), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), rhenium (Re), or thulium (Tm)),

[0522] L_{401} may be a ligand represented by Formula 402, and xc1 may be 1, 2, or 3, wherein when xc1 is 2 or more, two or more of L_{401} may be identical to or different from each other,

[0523] L_{402} may be an organic ligand, and $xc2$ may be 0, 1, 2, 3, or 4, wherein when $xc2$ is 2 or more, two or more of L_{402} may be identical to or different from each other,

[0524] X_{401} and X_{402} may each independently be nitrogen or carbon,

[0525] ring A_{401} and ring A_{402} may each independently be a C_3 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group,

[0526] T_{401} may be a single bond, $*-O-*$, $*-S-*$, $*-C(=O)-*$, $*-N(Q_{411})-*$, $*-C(Q_{411})(Q_{412})-*$, $*-C(Q_{411})=C(Q_{412})-*$, $*-C(Q_{411})=*$, or $*=C=*$,

[0527] X_{403} and X_{404} may each independently be a chemical bond (e.g., a covalent bond or a coordinate bond), O, S, $N(Q_{413})$, $B(Q_{413})$, $P(Q_{413})$, $C(Q_{413})(Q_{414})$, or $Si(Q_{413})(Q_{414})$,

[0528] Q_{411} to Q_{414} may each independently be the same as described in connection with Q_1 ,

[0529] R_{401} and R_{402} may each independently be hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{20} alkoxy group unsubstituted or substituted with at least one R_{10a} , a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , $-Si(Q_{401})(Q_{402})(Q_{403})$, $-N(Q_{401})(Q_{402})$, $-B(Q_{401})(Q_{402})$, $-C(=O)(Q_{401})$, $-S(=O)_2(Q_{401})$, or $-P(=O)(Q_{401})(Q_{402})$,

[0530] Q_{401} to Q_{403} may each independently be the same as described in connection with Q_1 ,


[0531] $xc11$ and $xc12$ may each independently be an integer from 0 to 10, and $*$ and $*$ in Formula 402 each indicate a binding site to M in Formula 401.

[0532] In an embodiment, in Formula 402, X_{401} may be nitrogen and X_{402} may be carbon, or X_{401} and X_{402} may each be nitrogen.


[0533] In embodiments, in Formula 401, when $xc1$ is 2 or more, two of ring A_{401} among two or more of L_{401} may optionally be linked to each other via T_{402} , which is a linking group, and two of ring A_{402} among two or more of L_{401} may optionally be linked to each other via T_{403} , which is a linking group (see Compounds PD1 to PD4 and PD7). T_{402} and T_{403} may each independently be the same as described in connection with T_{401} .

[0534] In Formula 401, L_{402} may be an organic ligand. In an embodiment, L_{402} may include a halogen group, a diketone group (e.g., an acetylacetonate group), a carboxylic acid group (e.g., a picolinate group), $-C(=O)$, an isonitrile group, a α -CN group, a phosphorus group (e.g., a phosphine group, a phosphite group, etc.), or any combination thereof.


[0535] In an embodiment, the phosphorescent dopant may include, for example, one of Compounds PD1 to PD39, or any combination thereof:




PD1




PD2



PD3




PD4



PD5

-continued



-continued

PD6

PD12


PD7

PD8

PD9

PD10

PD11




PD13

PD14


PD15

PD16


-continued




PD17




PD18



PD19




PD20




PD21


-continued




PD22



PD23




PD24




PD25

-continued




PD26

-continued




PD30

PD27





PD31

PD28




PD32

PD29




-continued


PD33




PD34



PD35




PD36




-continued


PD37



PD38



PD39



[Fluorescent Dopant]



[0536] In an embodiment, when the emission layer includes the heterocyclic compound as described herein and the heterocyclic compound serves as an auxiliary dopant or a sensitizer, the emission layer may further include a fluorescent dopant.

[0537] In embodiments, when the emission layer includes the heterocyclic compound as described herein and the

heterocyclic compound serves as a phosphorescent or fluorescent dopant, the emission layer may further include an auxiliary dopant.

[0538] The fluorescent dopant and the auxiliary dopant (or sensitizer) may each independently include an arylamine compound, a styrylamine compound, a boron-containing compound, or any combination thereof.

[0539] In an embodiment, the fluorescent dopant and the auxiliary dopant may each independently include a compound represented by Formula 501:



FD1

FD2

FD3

FD4

[0540] In Formula 501,

[0541] Ar_{501} , L_{501} to L_{503} , R_{501} , and R_{502} may each independently be a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,


[0542] xd1 to xd3 may each independently be 0, 1, 2, or 3, and

[0543] xd4 may be 1, 2, 3, 4, 5, or 6.


[0544] In an embodiment, in Formula 501, Ar_{501} may be a condensed cyclic group (e.g., an anthracene group, a chrysene group, a pyrene group, etc.) in which three or more monocyclic groups are condensed with each other.

[0545] In embodiments, in Formula 501, xd4 may be 2.


[0546] In an embodiment, the fluorescent dopant and the auxiliary dopant may each independently include one of Compounds FD1 to FD37, DPVBi, DPAVB, or any combination thereof:



-continued
FD5





FD6





FD7

FD8





FD9

FD10




FD11


FD12




-continued
FD13




FD14




FD15




FD16




FD17




FD18



FD19




FD20




-continued


FD21




FD22




FD23




FD24




FD25




FD26




FD27




FD28




FD29




FD30




-continued
FD31




FD32




FD33




FD34





FD35




FD36



FD37



DPVBi



DPAVBi

[Delayed Fluorescence Material]

[0547] In an embodiment, the emission layer may include a delayed fluorescence material.

[0548] In the specification, a delayed fluorescence material may be any compound that is capable of emitting delayed fluorescence, based on a delayed fluorescence emission mechanism.



[0549] The delayed fluorescence material may include, for example, the fourth compound as described herein.

[0550] The delayed fluorescence material included in the emission layer may serve as a host or as a dopant, depending on the types of other materials included in the emission layer.




[0551] In an embodiment, a difference between a triplet energy level (eV) of the delayed fluorescence material and a singlet energy level (eV) of the delayed fluorescence material may be in a range of about 0 eV to about 0.5 eV. When the difference between the triplet energy level (eV) of the delayed fluorescence material and the singlet energy level (eV) of the delayed fluorescence material is within the range described above, up-conversion from a triplet state to a singlet state of the delayed fluorescence material may effectively occur, and thus, the light-emitting device may have improved luminescence efficiency.

[0552] In an embodiment, the delayed fluorescence material may include: a material including at least one electron donor (e.g., a π electron-rich C_3 - C_{60} cyclic group, such as a carbazole group, etc.) and at least one electron acceptor (e.g., a sulfoxide group, a cyano group, a Ir electron-deficient nitrogen-containing C_1 - C_{60} cyclic group, etc.); or a material including a C_8 - C_{60} polycyclic group including two or more cyclic groups that are condensed with each other while sharing B; or the like.


[0553] In an embodiment, the delayed fluorescence material may include, for example, at least one of Compounds DF1 to DF14:



-continued




-continued



(PIC-TRZ2)


DF6

-continued




DF10

DF7




(PXZ-TRZ)

DF11




DF12


DF8



(DABNA-1)




DF9




(DABNA-2)

DF13



-continued

DF14



[Quantum Dot]

[0554] In an embodiment, the emission layer may include a quantum dot.

[0555] In the specification, a quantum dot may be a crystal of a semiconductor compound, and may include any material capable of emitting light of various emission wavelengths according to a size of the crystal.

[0556] A diameter of the quantum dot may be, for example, in a range of about 1 nm to about 10 nm.

[0557] The quantum dot may be synthesized by a wet chemical process, a metal organic chemical vapor deposition process, a molecular beam epitaxy process, or any process similar thereto.

[0558] The wet chemical process is a method that includes mixing a precursor material with an organic solvent and growing a quantum dot particle crystal. When the crystal grows, the organic solvent naturally serves as a dispersant coordinated on the surface of the quantum dot crystal and controls the growth of the crystal so that the growth of quantum dot particles may be controlled through a process which costs less and may be more readily performed than vapor deposition methods, such as metal organic chemical vapor deposition (MOCVD) or molecular beam epitaxy (MBE).

[0559] The quantum dot may include a Group II-VI semiconductor compound, a Group III-V semiconductor compound, a Group III-VI semiconductor compound, a Group I-III-VI semiconductor compound, a Group IV-VI semiconductor compound, a Group IV element or compound, or any combination thereof.

[0560] Examples of a Group II-VI semiconductor compound may include: a binary compound, such as CdS, CdSe, CdTe, ZnS, ZnSe, ZnTe, ZnO, HgS, HgSe, HgTe, MgSe, MgS, or the like; a ternary compound, such as CdSeS, CdSeTe, CdSbTe, ZnSeS, ZnSeTe, ZnSbTe, HgSeS, HgSeTe, HgSbTe, CdZnS, CdZnSe, CdZnTe, CdHgS, CdHgSe, CdHgTe, HgZnS, HgZnSe, HgZnTe, MgZnS, MgZnSe, or the like; a quaternary compound, such as CdZnSeS, CdZnSeTe, CdZnSbTe, CdHgSeS, CdHgSeTe, CdHgSbTe, HgZnSeS, HgZnSeTe, HgZnSbTe, or the like; and any combination thereof.

[0561] Examples of a Group III-V semiconductor compound may include: a binary compound, such as GaN, GaP, GaAs, GaSb, AlN, AlP, AlAs, AlSb, InN, InP, InAs, InSb, or the like; a ternary compound, such as GaNP, GaNAS, GaNSb, GaPAS, GaPSb, AlNP, AlNAs, AlNSb, AIPAS,

AIPbSb, InGaP, InNP, InAlP, InNAs, InNSb, InPAs, InPSb, or the like; a quaternary compound, such as GaAlNP, GaAlNAs, GaAlNSb, GaAIPAS, GaAIPbSb, GalnNP, GalnNAs, GalnNSb, GalnPAs, GalnPbSb, InAlNP, InAlNAs, InAlNSb, InAlPAs, InAlPSb, or the like; and any combination thereof. In an embodiment, a Group III-V semiconductor compound may further include a Group II element. Examples of a Group III-V semiconductor compound further including a Group II element may include InZnP, InGaZnP, InAlZnP, and the like.

[0562] Examples of a Group III-VI semiconductor compound may include: a binary compound, such as GaS, Ga₂Se, Ga₂Se₃, GaTe, InS, InSe, In₂S₃, In₂Se₃, InTe, or the like; a ternary compound, such as InGaS₃, InGaSe₃, or the like; and any combination thereof.

[0563] Examples of a Group I-III-VI semiconductor compound may include: a ternary compound, such as AgInS, AgInS₂, CuInS, CuInS₂, CuGaO₂, AgGaO₂, AgAlO₂, or the like; and any combination thereof.

[0564] Examples of a Group IV-VI semiconductor compound may include: a binary compound, such as SnS, SnSe, SnTe, PbS, PbSe, PbTe, or the like; a ternary compound, such as SnSeS, SnSeTe, SnSbTe, PbSeS, PbSeTe, PbSbTe, SnPbS, SnPbSe, SnPbTe, or the like; a quaternary compound, such as SnPbSSe, SnPbSeTe, SnPbSbTe, or the like; and any combination thereof.

[0565] Examples of a Group IV element or compound may include: a single element material, such as Si, Ge, or the like; a binary compound, such as SiC, SiGe, or the like; and any combination thereof.

[0566] Each element included in a compound, such as a binary compound, a ternary compound, or a quaternary compound, may be present in a particle at a uniform concentration or at a non-uniform concentration.

[0567] In an embodiment, the quantum dot may have a single structure in which the concentration of each element in the quantum dot is uniform, or the quantum dot may have a core-shell structure. For example, a material included in the core and a material included in the shell may be different from each other.

[0568] The shell of the quantum dot may serve as a protective layer that prevents chemical degeneration of the core to maintain semiconductor characteristics, and/or may serve as a charging layer that imparts electrophoretic characteristics to the quantum dot. The shell may be single-layered or multilayered. An interface between the core and the shell may have a concentration gradient in which the concentration of a material that is present in the shell decreases toward the core.

[0569] Examples of a shell of a quantum dot may include a metal oxide, a metalloid oxide, a non-metal oxide, a semiconductor compound, or any combination thereof. Examples of a metal oxide, a metalloid oxide, or a non-metal oxide may include: a binary compound, such as SiO₂, Al₂O₃, TiO₂, ZnO, MnO, Mn₂O₃, Mn₃O₄, CuO, FeO, Fe₂O₃, Fe₃O₄, CoO, Co₃O₄, NiO, or the like; a ternary compound, such as MgAl₂O₄, CoFe₂O₄, NiFe₂O₄, CoMn₂O₄, or the like; and any combination thereof.

[0570] Examples of a semiconductor compound may include, as described herein, a Group II-VI semiconductor compound, a Group III-V semiconductor compound, a Group III-VI semiconductor compound, a Group I-III-VI semiconductor compound, a Group IV-VI semiconductor compound, and any combination thereof. For example, a

semiconductor compound may include CdS, CdSe, CdTe, ZnS, ZnSe, ZnTe, ZnSeS, ZnTeS, GaAs, GaP, GaSb, HgS, HgSe, HgTe, InAs, InP, InGaP, InSb, AlAs, AlP, AISb, or any combination thereof.

[0571] The quantum dot may have a full width at half maximum (FWHM) of an emission wavelength spectrum less than or equal to about 45 nm. For example, the quantum dot may have a FWHM of an emission wavelength spectrum less than or equal to about 40 nm. For example, the quantum dot may have a FWHM of an emission wavelength spectrum less than or equal to about 30 nm. When the FWHM of the quantum dot is within any of these ranges, the quantum dot may have improved color purity or improved color reproducibility. Light emitted through the quantum dot may be emitted in all directions, so that a wide viewing angle may be improved.

[0572] In an embodiment, the quantum dot may be in the form of a spherical particle, a pyramidal particle, a multi-arm particle, a cubic nanoparticle, a nanotube particle, a nanowire particle, a nanofiber particle, a nanoplate particle, or the like.

[0573] Since an energy band gap may be adjusted by controlling a size of the quantum dot, light having various wavelength bands may be obtained from a quantum dot emission layer. Accordingly, by using quantum dots of different sizes, a light-emitting device that emits light of various wavelengths may be implemented. In an embodiment, the size of the quantum dot may be selected to emit red light, green light, and/or blue light. In an embodiment, the size of the quantum dot may be configured to emit white light by a combination of light of various colors.

[Electron Transport Region in Interlayer 130]


[0574] The electron transport region may have a structure consisting of a layer consisting of a single material, a structure consisting of a layer including different materials, or a structure including multiple layers including different materials.

[0575] The electron transport region may include a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, an electron injection layer, or any combination thereof.

[0576] In an embodiment, the electron transport region may have an electron transport layer/electron injection layer structure, a hole blocking layer/electron transport layer/electron injection layer structure, an electron control layer/electron transport layer/electron injection layer structure, or a buffer layer/electron transport layer/electron injection layer structure, wherein the layers of each structure may be stacked from the emission layer in its respective stated order, but the structure of the electron transport region is not limited thereto.

[0577] The electron transport region (e.g., a buffer layer, a hole blocking layer, an electron control layer, or an electron transport layer in the electron transport region) may include a metal-free compound including at least one π electron-deficient nitrogen-containing C_1 - C_{60} heterocyclic group.

[0578] In an embodiment, the electron transport region may include a compound represented by Formula 601:



In Formula 601,

[0579] Ar_{601} and L_{601} may each independently be a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,

[0580] $xe11$ may be 1, 2, or 3,

[0581] $xe1$ may be 0, 1, 2, 3, 4, or 5,

[0582] R_{601} may be a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , $-\text{Si}(Q_{601})(Q_{602})(Q_{603})$, $-\text{C}(=\text{O})(Q_{601})$, $-\text{S}(=\text{O})_2(Q_{601})$, or $-\text{P}(=\text{O})(Q_{601})(Q_{602})$,

[0583] Q_{601} to Q_{603} may each independently be the same as described in connection with Q_1 ,

[0584] $xe21$ may be 1, 2, 3, 4, or 5, and


[0585] at least one of Ar_{601} , L_{601} , and R_{601} may each independently be a π electron-deficient nitrogen-containing C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} .

[0586] In an embodiment, in Formula 601, when $xe11$ is 2 or more, two or more of Ar_{601} may be linked to each other via a single bond.

[0587] In embodiments, in Formula 601, Ar_{601} may be a substituted or unsubstituted anthracene group.

[0588] In embodiments, the electron transport region may include a compound represented by Formula 601-1:

[Formula 601-1]



[0589] In Formula 601-1,

[0590] X_{614} may be N or C(R_{614}), X_{615} may be N or C(R_{615}), X_{616} may be N or C(R_{616}), and at least one of X_{614} to X_{616} may each be N,

[0591] L_{611} to L_{613} may each independently be the same as described in connection with L_{601} ,

[0592] $xe611$ to $xe613$ may each independently be the same as described in connection with $xe1$,



[0593] R_{611} to R_{613} may each independently be the same as described in connection with R_{601} , and

[0594] R_{614} to R_{616} may each independently be hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} .





[0595] In an embodiment, in Formulae 601 and 601-1, $xe1$ and $xe611$ to $xe613$ may each independently be 0, 1, or 2.

[0596] The electron transport region may include one of Compounds ET1 to ET45, 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), Alq₃, BAlq, TAZ, NTAZ, or any combination thereof:


-continued

ET2


ET5



ET3




-continued




ET8

-continued




ET9

ET11




ET10

ET12




ET13

-continued




ET14

-continued




ET17


ET15




ET18




ET16



ET19




-continued




ET20

-continued




ET23


ET21




ET24



ET22




ET25




-continued

ET26




-continued


ET29




ET27




ET30




ET28



ET31




-continued




ET32


-continued




ET35




ET33




ET36



ET37




ET34




ET38

-continued




ET39


-continued




ET42




ET40




ET43



ET41



ET44



[0597] A thickness of the electron transport region may be in a range of about 100 Å to about 5,000 Å. For example, the thickness of the electron transport region may be in a range of about 160 Å to about 4,000 Å. When the electron transport region includes a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, or any combination thereof, a thickness of the buffer layer, the hole blocking layer, or the electron control layer may each independently be in a range of about 20 Å to about 1,000 Å, and a thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å. For example, the thickness of the buffer layer, the hole blocking layer, or the electron control layer may each independently be in a range of about 30 Å to about 300 Å. For example, the thickness of the electron transport layer may be in a range of about 150 Å to about 500 Å. When the thicknesses of the buffer layer, the hole blocking layer, the electron control layer, the


electron transport layer, and/or the electron transport region are within the ranges described above, satisfactory electron transporting characteristics may be obtained without a substantial increase in driving voltage.

[0598] The electron transport region (e.g., an electron transport layer in the electron transport region) may further include, in addition to the materials described above, a metal-containing material.

[0599] The metal-containing material may include an alkali metal complex, an alkaline earth metal complex, or any combination thereof. A metal ion of the alkali metal complex may be a Li ion, a Na ion, a K ion, a Rb ion, or a Cs ion, and a metal ion of the alkaline earth metal complex may be a Be ion, a Mg ion, a Ca ion, a Sr ion, or a Ba ion.

[0600] A ligand coordinated with a metal ion of an alkali metal complex or an alkaline earth-metal complex may each independently include a hydroxyquinoline, a hydroxyisoquinoline, a hydroxybenzoquinoline, a hydroxyacridine, a hydroxyphenanthridine, a hydroxyphenyloxazole, a hydroxyphenylthiazole, a hydroxyphenyloxadiazole, a hydroxyphenylthiadiazole, a hydroxyphenylpyridine, a hydroxyphenylbenzimidazole, a hydroxyphenylbenzothiazole, a bipyridine, a phenanthroline, a cyclopentadiene, or any combination thereof.

[0601] In an embodiment, the metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (LiQ) or Compound ET-D2:



[0602] The electron transport region may include an electron injection layer that facilitates the injection of electrons from the second electrode 150. The electron injection layer may contact (e.g., directly contact) the second electrode 150.

[0603] The electron injection layer may have a structure consisting of a layer consisting of a single material, a structure consisting of a layer including different materials, or a structure including multiple layers including different materials.

[0604] In an embodiment, the electron injection layer may include an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal-containing compound, an alkaline earth metal-containing compound, a rare earth metal-containing compound, an alkali metal complex, an alkaline earth metal complex, a rare earth metal complex, or any combination thereof.

[0605] The alkali metal may include Li, Na, K, Rb, Cs, or any combination thereof. The alkaline earth metal may include Mg, Ca, Sr, Ba, or any combination thereof. The rare earth metal may include Sc, Y, Ce, Tb, Yb, Gd, or any combination thereof.

[0606] The alkali metal-containing compound, the alkaline earth metal-containing compound, and the rare earth metal-containing compound may include oxides, halides (e.g., fluorides, chlorides, bromides, iodides, etc.), or tellurides of the alkali metal, the alkaline earth metal, and the rare earth metal, or any combination thereof.

[0607] The alkali metal-containing compound may include: an alkali metal oxide, such as Li_2O , Cs_2O , K_2O , or the like; an alkali metal halide, such as LiF , NaF , CsF , KF , LiI , NaI , CsI , KI , RbI , or the like; or any combination thereof. The alkaline earth metal-containing compound may include an alkaline earth metal oxide, such as BaO , SrO , CaO , $\text{Ba}_{1-x}\text{Sr}_x\text{O}$ (wherein x is a real number satisfying $0 < x < 1$), $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ (wherein x is a real number satisfying $0 < x < 1$), or the like. The rare earth metal-containing compound may include YbF_3 , ScF_3 , SC_2O_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , TbF_3 , YbI_3 , ScI_3 , TbI_3 , or any combination thereof. In an embodiment, the rare earth metal-containing compound may include a lanthanide metal telluride. Examples of a lanthanide metal telluride may include LaTe , CeTe , PrTe , NdTe , PmTe , SmTe , EuTe , GdTe , TbTe , DyTe , HoTe , ErTe , TmTe , YbTe , LuTe , La_2Te_3 , Ce_2Te_3 , Pr_2Te_3 , Nd_2Te_3 , Pm_2Te_3 , Sm_2Te_3 , Eu_2Te_3 , Gd_2Te_3 , Tb_2Te_3 , Dy_2Te_3 , Ho_2Te_3 , Er_2Te_3 , Tm_2Te_3 , Yb_2Te_3 , Lu_2Te_3 , and the like.

[0608] The alkali metal complex, the alkaline earth-metal complex, and the rare earth metal complex may include: an alkali metal ion, an alkaline earth metal ion, or a rare earth metal ion; and a ligand bonded to the metal ion (for example, a hydroxyquinoline, a hydroxyisoquinoline, a hydroxybenzoquinoline, a hydroxyacridine, a hydroxyphenanthridine, a hydroxyphenylthiazole, a hydroxyphenylthiadiazole, a hydroxyphenylpyridine, a hydroxyphenylbenzimidazole, a hydroxyphenylbenzothiazole, a bipyridine, a phenanthroline, a cyclopentadiene, or any combination thereof).

[0609] In an embodiment, the electron injection layer may consist of an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal-containing compound, an alkaline earth metal-containing compound, a rare earth metal-containing compound, an alkali metal complex, an alkaline earth metal complex, a rare earth metal complex, or any combination thereof, as described above. In embodiments, the electron injection layer may further include an organic material (e.g., a compound represented by Formula 601).

[0610] In an embodiment, the electron injection layer may consist of an alkali metal-containing compound (e.g., an alkali metal halide); or the electron injection layer may consist of an alkali metal-containing compound (e.g., an alkali metal halide), and an alkali metal, an alkaline earth metal, a rare earth metal, or any combination thereof. In an embodiment, the electron injection layer may be a $\text{KI}:\text{Yb}$ co-deposited layer, an $\text{RbI}:\text{Yb}$ co-deposited layer, a $\text{LiF}:\text{Yb}$ co-deposited layer, or the like.

[0611] When the electron injection layer further includes an organic material, the alkali metal, the alkaline earth metal, the rare earth metal, the alkali metal-containing compound, the alkaline earth metal-containing compound, the rare earth metal-containing compound, the alkali metal complex, the alkaline earth-metal complex, the rare earth

metal complex, or any combination thereof may be uniformly or non-uniformly dispersed in a matrix including the organic material.

[0612] A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å. For example, the thickness of the electron injection layer may be in a range of about 3 Å to about 90 Å. When the thickness of the electron injection layer is within any of the ranges described above, satisfactory electron injection characteristics may be obtained without a substantial increase in driving voltage.

[Second Electrode 150]

[0613] The second electrode 150 may be arranged on the interlayer 130 having a structure as described above. The second electrode 150 may be a cathode, which is an electron injection electrode. When the second electrode 150 is a cathode, a material for forming the second electrode may include a material having a low-work function, such as a metal, an alloy, an electrically conductive compound, or any combination thereof.

[0614] The second electrode 150 may include lithium (Li), silver (Ag), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), ytterbium (Yb), silver-ytterbium (Ag—Yb), ITO, IZO, or any combination thereof. The second electrode 150 may be a transmissive electrode, a transfective electrode, or a reflective electrode.

[0615] The second electrode 150 may have a single-layer structure or a multi-layer structure.

[Capping Layer]

[0616] The light-emitting device 10 may include a first capping layer outside the first electrode 110, and/or a second capping layer outside the second electrode 150. In embodiments, the light-emitting device 10 may have a structure in which the first capping layer, the first electrode 110, the interlayer 130, and the second electrode 150 are stacked in this stated order, a structure in which the first electrode 110, the interlayer 130, the second electrode 150, and the second capping layer are stacked in this stated order, or a structure in which the first capping layer, the first electrode 110, the interlayer 130, the second electrode 150, and the second capping layer are stacked in this stated order.

[0617] Light generated in the emission layer of the interlayer 130 of the light-emitting device 10 may be extracted through the first electrode 110, which may be a transfective electrode or a transmissive electrode, and through the first capping layer to the outside. Light generated in the emission layer of the interlayer 130 of the light-emitting device 10 may be extracted through the second electrode 150, which may be a transfective electrode or a transmissive electrode, and through the second capping layer to the outside.

[0618] The first capping layer and the second capping layer may each increase external emission efficiency according to the principle of constructive interference. Accordingly, the light-extraction efficiency of the light-emitting device 10 may be increased, so that the luminescence efficiency of the light-emitting device 10 may be improved.

[0619] The first capping layer and the second capping layer may each include a material having a refractive index greater than or equal to about 1.6 (with respect to a wavelength of about 589 nm).

[0620] The first capping layer and the second capping layer may each independently be an organic capping layer including an organic material, an inorganic capping layer including an inorganic material, or an organic-inorganic composite capping layer including an organic material and an inorganic material.

[0621] At least one of the first capping layer and the second capping layer may each independently include a carbocyclic compound, a heterocyclic compound, an amine group-containing compound, a porphine derivative, a phthalocyanine derivative, a naphthalocyanine derivative, an alkali metal complex, an alkaline earth metal complex, or any combination thereof. The carbocyclic compound, the heterocyclic compound, and the amine group-containing compound may optionally be substituted with a substituent including O, N, S, Se, Si, F, Cl, Br, I, or any combination thereof.


[0622] In an embodiment, at least one of the first capping layer and the second capping layer may each independently include an amine group-containing compound.

[0623] In an embodiment, at least one of the first capping layer and the second capping layer may each independently include a compound represented by Formula 201, a compound represented by Formula 202, or any combination thereof.


[0624] In embodiments, at least one of the first capping layer and the second capping layer may each independently include one of Compounds HT28 to HT33, one of Compounds CP1 to CP6, β -NPB, or any combination thereof:

-continued


CP3




CP4




CP1



CP2




CP5



-continued

CP6



[Film]

[0625] The heterocyclic compound may be included in various films. Accordingly, another embodiment provides a film including the heterocyclic compound. The film may be, for example, an optical member (or a light control means) (e.g., a color filter, a color conversion member, a capping layer, a light extraction efficiency enhancement layer, a selective light absorbing layer, a polarizing layer, a quantum dot-containing layer, etc.), a light blocking member (e.g., a light reflective layer, a light absorbing layer, etc.), a protective member (e.g., an insulating layer, a dielectric layer, etc.), or the like.

[Electronic Apparatus]

[0626] The light-emitting device may be included in various electronic apparatuses. For example, an electronic apparatus including the light-emitting device may be a light-emitting apparatus, an authentication apparatus, or the like.

[0627] The electronic apparatus (e.g., a light-emitting apparatus) may further include, in addition to the light-emitting device, a color filter, a color conversion layer, or a color filter and a color conversion layer. The color filter and/or the color conversion layer may be arranged in at least one traveling direction of light emitted from the light-emitting device. For example, light emitted from the light-emitting device may be blue light, green light, or white light. The light-emitting device may be the same as described herein. In an embodiment, the color conversion layer may include a quantum dot.

[0628] The electronic apparatus may include a substrate. The substrate may include subpixels, the color filter may include color filter areas respectively corresponding to the subpixels, and the color conversion layer may include color conversion areas respectively corresponding to the subpixels.

[0629] A pixel-defining film may be arranged between the subpixels to define each subpixel.

[0630] The color filter may further include color filter areas and light-shielding patterns arranged between the color filter areas, and the color conversion layer may further include color conversion areas and light-shielding patterns arranged between the color conversion areas.

[0631] The color filter areas (or the color conversion areas) may include a first area emitting first color light, a second area emitting second color light, and/or a third area emitting third color light, wherein the first color light, the second color light, and/or the third color light may have different maximum emission wavelengths from one another. In an embodiment, the first color light may be red light, the second color light may be green light, and the third color light may be blue light. In an embodiment, the color filter areas (or the color conversion areas) may include quantum dots. In an embodiment, the first area may include a red quantum dot, the second area may include a green quantum dot, and the third area may not include a quantum dot. The quantum dot may be the same as described herein. The first area, the second area, and/or the third area may each further include a scatterer.

[0632] In an embodiment, the light-emitting device may emit first light, the first area may absorb the first light to emit first-first color light, the second area may absorb the first light to emit second-first color light, and the third area may absorb the first light to emit third-first color light. The first-first color light, the second-first color light, and the third-first color light may have different maximum emission wavelengths. In an embodiment, the first light may be blue light, the first-first color light may be red light, the second-first color light may be green light, and the third-first color light may be blue light.

[0633] The electronic apparatus may further include a thin-film transistor, in addition to the light-emitting device as described above. The thin-film transistor may include a source electrode, a drain electrode, and an active layer, wherein any one of the source electrode and the drain electrode may be electrically connected to any one of the first electrode and the second electrode of the light-emitting device.

[0634] The thin-film transistor may further include a gate electrode, a gate insulating film, and the like.

[0635] The active layer may include crystalline silicon, amorphous silicon, an organic semiconductor, an oxide semiconductor, and the like.

[0636] The electronic apparatus may further include a sealing portion for sealing the light-emitting device. The sealing portion may be arranged between the color filter and/or the color conversion layer and the light-emitting device. The sealing portion may allow light from the light-emitting device to be extracted to the outside, and may prevent ambient air and moisture from penetrating into the light-emitting device. The sealing portion may be a sealing substrate that includes a transparent glass substrate or a plastic substrate. The sealing portion may be a thin-film encapsulation layer that includes at least one of an organic

layer and/or an inorganic layer. When the sealing portion is a thin-film encapsulation layer, the electronic apparatus may be flexible.

[0637] Various functional layers may be further included on the sealing portion, in addition to the color filter and/or the color conversion layer, according to a use of the electronic apparatus. Examples of a functional layer may include a touch screen layer, a polarizing layer, and the like. The touch screen layer may be a pressure-sensitive touch screen layer, a capacitive touch screen layer, or an infrared touch screen layer. The authentication apparatus may be, for example, a biometric authentication apparatus that authenticates an individual by using biometric information of a living body (e.g., fingertips, pupils, etc.).

[0638] The authentication apparatus may further include, in addition to the light-emitting device as described above, a biometric information collector.

[0639] The electronic apparatus may be applied to various displays, light sources, lighting, personal computers (e.g., a mobile personal computer), mobile phones, digital cameras, electronic organizers, electronic dictionaries, electronic game machines, medical instruments (e.g., electronic thermometers, sphygmomanometers, blood glucose meters, pulse measurement devices, pulse wave measurement devices, electrocardiogram displays, ultrasonic diagnostic devices, or endoscope displays), fish finders, various measuring instruments, meters (e.g., meters for a vehicle, an aircraft, and a vessel), projectors, and the like.

[Electronic Equipment]

[0640] The light-emitting device may be included in various electronic equipment.

[0641] In embodiments, an electronic equipment including the light-emitting device may be a flat panel display, a curved display, a computer monitor, a medical monitor, a television, a billboard, an indoor light, an outdoor light, a signal light, a head-up display, a fully transparent display, a partially transparent display, a flexible display, a rollable display, a foldable display, a stretchable display, a laser printer, a telephone, a mobile phone, a tablet computer, a phablet, a personal digital assistant (PDA), a wearable device, a laptop computer, a digital camera, a camcorder, a viewfinder, a micro display, a three-dimensional (3D) display, a virtual reality display, an augmented reality display, a vehicle, a video wall with multiple displays tiled together, a theater screen, a stadium screen, a phototherapy device, or a signboard.

[0642] The light-emitting device may have excellent luminescence efficiency and long lifespan, and thus, the electronic equipment including the light-emitting device may have characteristics such as high luminance, high resolution, and low power consumption.

[Descriptions of FIGS. 2 and 3]

[0643] FIG. 2 is a schematic cross-sectional view of an electronic apparatus (e.g., a light-emitting apparatus) according to an embodiment.

[0644] The electronic apparatus of FIG. 2 may include a substrate 100, a thin-film transistor (TFT), a light-emitting device, and an encapsulation portion 300 that seals the light-emitting device.

[0645] The substrate 100 may be a flexible substrate, a glass substrate, or a metal substrate. A buffer layer 210 may

be arranged on the substrate 100. The buffer layer 210 may prevent penetration of impurities through the substrate 100, and may provide a flat surface on the substrate 100.

[0646] A TFT may be arranged on the buffer layer 210. The TFT may include an active layer 220, a gate electrode 240, a source electrode 260, and a drain electrode 270.

[0647] The active layer 220 may include an inorganic semiconductor, such as silicon or polysilicon, an organic semiconductor, or an oxide semiconductor, and may include a source region, a drain region, and a channel region.

[0648] A gate insulating film 230 for insulating the active layer 220 from the gate electrode 240 may be arranged on the active layer 220, and the gate electrode 240 may be arranged on the gate insulating film 230.

[0649] An interlayer insulating film 250 may be arranged on the gate electrode 240. The interlayer insulating film 250 may be arranged between the gate electrode 240 and the source electrode 260 to insulate the gate electrode 240 from the source electrode 260 and between the gate electrode 240 and the drain electrode 270 to insulate the gate electrode 240 from the drain electrode 270.

[0650] The source electrode 260 and the drain electrode 270 may be arranged on the interlayer insulating film 250. The interlayer insulating film 250 and the gate insulating film 230 may be formed to expose a source region and a drain region of the active layer 220, and the source electrode 260 and the drain electrode 270 may respectively contact the exposed portions of the source region and the drain region of the active layer 220.

[0651] The TFT may be electrically connected to a light-emitting device to drive the light-emitting device, and may be covered and protected by a passivation layer 280. The passivation layer 280 may include an inorganic insulating film, an organic insulating film, or any combination thereof. A light-emitting device may be provided on the passivation layer 280. The light-emitting device may include the first electrode 110, the interlayer 130, and the second electrode 150.

[0652] The first electrode 110 may be arranged on the passivation layer 280. The passivation layer 280 may not completely cover the drain electrode 270 and may expose a portion of the drain electrode 270. The first electrode 110 may be connected (for example, electrically connected) to the exposed portion of the drain electrode 270.

[0653] A pixel-defining film 290 including an insulating material may be arranged on the first electrode 110. The pixel-defining film 290 may expose a region of the first electrode 110, and the interlayer 130 may be formed on the exposed region of the first electrode 110. The pixel-defining film 290 may be a polyimide-based organic film or a polyacrylic organic film. Although not shown in FIG. 2, at least some layers of the interlayer 130 may extend beyond the upper portion of the pixel-defining film 290 to be provided in the form of a common layer.

[0654] The second electrode 150 may be arranged on the interlayer 130, and a second capping layer 170 may be further included on the second electrode 150. The second capping layer 170 may be formed to cover the second electrode 150.

[0655] The encapsulation portion 300 may be arranged on the second capping layer 170. The encapsulation portion 300 may be arranged on a light-emitting device to protect the light-emitting device from moisture and/or oxygen. The encapsulation portion 300 may include: an inorganic film

including silicon nitride (SiNx), silicon oxide (SiOx), indium tin oxide, indium zinc oxide, or any combination thereof; an organic film including polyethylene terephthalate, polyethylene naphthalate, polycarbonate, polyimide, polyethylene sulfonate, polyoxymethylene, polyarylate, hexamethyldisiloxane, an acrylic resin (e.g., polymethyl methacrylate, polyacrylic acid, etc.), an epoxy-based resin (e.g., aliphatic glycidyl ether (AGE), etc.), or any combination thereof; or any combination of the inorganic film and the organic film.

[0656] FIG. 3 is a schematic cross-sectional view of an electronic apparatus according to another embodiment.

[0657] The electronic apparatus of FIG. 3 may differ from the electronic apparatus of FIG. 2, at least in that a light-shielding pattern 500 and a functional region 400 are further included on the encapsulation portion 300. The functional region 400 may be a color filter area, a color conversion area, or a combination of the color filter area and the color conversion area. In an embodiment, the light-emitting device included in the electronic apparatus of FIG. 3 may be a tandem light-emitting device. [Description of FIG. 4]

[0658] FIG. 4 is a schematic perspective view of electronic equipment 1 including a light-emitting device according to an embodiment.

[0659] The electronic equipment 1, which may be an apparatus that displays a moving image or still image, may not only be a portable electronic equipment, such as a mobile phone, a smartphone, a tablet computer, a mobile communication terminal, an electronic notebook, an electronic book, a portable multimedia player (PMP), a navigation device, or an ultra-mobile PC (UMPC), but may also be various products, such as a television, a laptop, a monitor, a billboard, or an Internet of things (IoT). The electronic equipment 1 may be any product as described above or a part thereof.

[0660] In an embodiment, the electronic equipment 1 may be a wearable device, such as a smart watch, a watch phone, a glasses-type display, or a head mounted display (HMD), or a part of the wearable device. However, embodiments are not limited thereto.

[0661] Examples of the electronic equipment 1 may include a dashboard of a vehicle, a center information display (CID) arranged on a center fascia or dashboard of a vehicle, a room mirror display that replaces a side mirror of a vehicle, an entertainment display arranged for a rear seat of a vehicle or arranged on the back of a front seat, a head-up display (HUD) installed at the front of a vehicle or projected on a front window glass, or a computer generated hologram augmented reality head up display (CGH AR HUD). FIG. 4 illustrates an embodiment in which the electronic equipment 1 is a smartphone, for convenience of explanation.

[0662] The electronic equipment 1 may include a display area DA and a non-display area NDA outside the display area DA. A display apparatus may implement an image through a two-dimensional array of pixels that are arranged in the display area DA.

[0663] The non-display area NDA may be an area that does not display an image, and may surround (for example, entirely surround) the display area DA. A driver for providing electrical signals or power to display devices arranged on the display area DA may be arranged in the non-display area NDA. A pad, which is an area to which an electronic element or a printed circuit board may be electrically connected, may be arranged in the non-display area NDA.

[0664] In the electronic equipment 1, a length in an x-axis direction and a length in a y-axis direction may be different from each other. In an embodiment, as shown in FIG. 4, a length in the x-axis direction may be less than a length in the y-axis direction. In embodiments, a length in the x-axis direction may be the same as a length in the y-axis direction. In embodiments, a length in the x-axis direction may be longer than a length in the y-axis direction.

[Descriptions of FIGS. 5 and 6A to 6C]

[0665] FIG. 5 is a schematic perspective view of an exterior of a vehicle 1000 as an electronic equipment including the light-emitting device according to an embodiment. FIGS. 6A to 6C are each a schematic diagram of an interior of the vehicle 1000 according to embodiments.

[0666] Referring to FIGS. 5, 6A, 6B, and 6C, embodiments of a vehicle 1000 may include various apparatuses for moving a subject to be transported, such as a person, an object, or an animal, from a departure point to a destination point. Examples of a vehicle 1000 may include a vehicle traveling on a road or track, a vessel moving over the sea or river, an airplane flying in the sky using the action of air, and the like.

[0667] The vehicle 1000 may travel on a road or a track. The vehicle 1000 may move in a selectable direction according to the rotation of at least one wheel. Examples of a vehicle 1000 may include a three-wheeled or four-wheeled vehicle, a construction machine, a two-wheeled vehicle, a prime mover device, a bicycle, and a train running on a track.

[0668] The vehicle 1000 may include a vehicle body having an interior and an exterior, and a chassis that is a portion excluding the vehicle body in which mechanical apparatuses necessary for driving are installed. The exterior of the vehicle body may include a front panel, a bonnet, a roof panel, a rear panel, a trunk, a pillar provided at a boundary between doors, and the like. The chassis of the vehicle 1000 may include a power generating device, a power transmitting device, a driving device, a steering device, a braking device, a suspension device, a transmission device, a fuel device, front and rear wheels, left and right wheels, and the like.

[0669] The vehicle 1000 may include a side window glass 1100, a front window glass 1200, a side mirror 1300, a cluster 1400, a center fascia 1500, a passenger seat dashboard 1600, and a display apparatus 2.

[0670] The side window glass 1100 and the front window glass 1200 may be partitioned by a pillar arranged between the side window glass 1100 and the front window glass 1200.

[0671] The side window glass 1100 may be installed on a side of the vehicle 1000. In an embodiment, the side window glass 1100 may be installed on a door of the vehicle 1000. Multiple side window glasses 1100 may be provided and may face each other. In an embodiment, the side window glass 1100 may include a first side window glass 1110 and a second side window glass 1120. In an embodiment, the first side window glass 1110 may be arranged adjacent to the cluster 1400, and the second side window glass 1120 may be arranged adjacent to the passenger seat dashboard 1600.

[0672] In an embodiment, the side window glasses 1100 may be spaced apart from each other in the x-direction or the -x-direction. In an embodiment, the first side window glass 1110 and the second side window glass 1120 may be spaced

apart from each other in the x-direction or the -x-direction. For example, a virtual straight line L connecting the side window glasses 1100 may extend in the x-direction or the -x-direction. For example, a virtual straight line L connecting the first side window glass 1110 and the second side window glass 1120 to each other may extend in the x-direction or the -x-direction.

[0673] The front window glass 1200 may be installed in the front of the vehicle 1000. The front window glass 1200 may be arranged between the side window glasses 1100 facing each other.

[0674] The side mirror 1300 may provide a rear view of the vehicle 1000. The side mirror 1300 may be installed on the exterior of the vehicle body. In an embodiment, multiple side mirrors 1300 may be provided. For example, one of the side mirrors 1300 may be arranged outside the first side window glass 1110, and another of the side mirrors 1300 may be arranged outside the second side window glass 1120.

[0675] The cluster 1400 may be arranged in front of the steering wheel. The cluster 1400 may include a tachometer, a speedometer, a coolant thermometer, a fuel gauge, a turn signal indicator, a high beam indicator, a warning light, a seat belt warning light, an odometer, a tachograph, an automatic shift selector indicator light, a door open warning light, an engine oil warning light, and/or a low fuel warning light.

[0676] The center fascia 1500 may include a control panel on which buttons for adjusting an audio device, an air conditioning device, and a seat heater are arranged. The center fascia 1500 may be arranged on a side of the cluster 1400.

[0677] The passenger seat dashboard 1600 may be spaced apart from the cluster 1400, and the center fascia 1500 may be arranged between the cluster 1400 and the passenger seat dashboard 1600. In an embodiment, the cluster 1400 may be arranged to correspond to a driver seat (not shown), and the passenger seat dashboard 1600 may be arranged to correspond to a passenger seat (not shown). In an embodiment, the cluster 1400 may be adjacent to the first side window glass 1110, and the passenger seat dashboard 1600 may be adjacent to the second side window glass 1120.

[0678] In an embodiment, the display apparatus 2 may include a display panel 3, and the display panel 3 may display an image. The display apparatus 2 may be arranged inside the vehicle 1000. In an embodiment, the display apparatus 2 may be arranged between the side window glasses 1100 facing each other. The display apparatus 2 may be arranged on at least one of the cluster 1400, the center fascia 1500, and the passenger seat dashboard 1600.

[0679] The display apparatus 2 may include an organic light-emitting display apparatus, an inorganic light-emitting display apparatus, a quantum dot display apparatus, or the like. Hereinafter, an organic light-emitting display apparatus including the light-emitting device according to an embodiment will be described as an example of the display apparatus 2. However, various types of display apparatuses as described above may be used in embodiments.

[0680] Referring to FIG. 6A, the display apparatus 2 may be arranged on the center fascia 1500. In an embodiment, the display apparatus 2 may display navigation information. In an embodiment, the display apparatus 2 may display information regarding audio settings, video settings, or vehicle settings.

[0681] Referring to FIG. 6B, the display apparatus 2 may be arranged on the cluster 1400. In an embodiment, the cluster 1400 may display driving information and the like through the display apparatus 2. For example, the cluster 1400 may digitally implement driving information. The digital cluster 1400 may display vehicle information and driving information as images. For example, a needle and a gauge of a tachometer and various warning lights or icons may be displayed by a digital signal.

[0682] Referring to FIG. 6C, the display apparatus 2 may be arranged on the passenger seat dashboard 1600. The display apparatus 2 may be embedded in the passenger seat dashboard 1600 or arranged on the passenger seat dashboard 1600. In an embodiment, the display apparatus 2 arranged on the passenger seat dashboard 1600 may display an image related to information displayed on the cluster 1400 and/or information displayed on the center fascia 1500. In embodiments, the display apparatus 2 arranged on the passenger seat dashboard 1600 may display information that is different from information displayed on the cluster 1400 and/or information displayed on the center fascia 1500.

[Manufacturing Method]

[0683] The layers constituting the hole transport region, the emission layer, and the layers constituting the electron transport region may be formed in a selected region by using various methods such as vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, ink-jet printing, laser-printing, laser-induced thermal imaging, and the like.

[0684] When the layers constituting the hole transport region, the emission layer, and the layers constituting the electron transport region are formed by vacuum deposition, the deposition may be performed at a deposition temperature in a range of about 100° C. to about 500° C., at a vacuum degree in a range of about 10⁻⁸ torr to about 10⁻³ torr, and at a deposition speed in a range of about 0.01 Å/sec to about 100 Å/sec, depending on a material to be included in a layer to be formed and the structure of a layer to be formed.

[Definitions of Terms]

[0685] The term “C₃-C₆₀ carbocyclic group” as used herein may be a cyclic group consisting of carbon atoms as the only ring-forming atoms and having 3 to 60 carbon atoms. The term “C₁-C₆₀ heterocyclic group” as used herein may be a cyclic group that has 1 to 60 carbon atoms and further has, in addition to a carbon atom, at least one heteroatom as a ring-forming atom. The C₃-C₆₀ carbocyclic group and the C₁-C₆₀ heterocyclic group may each be a monocyclic group consisting of one ring or a polycyclic group in which two or more rings are condensed with each other. For example, the number of ring-forming atoms in a C₁-C₆₀ heterocyclic group may be from 3 to 61.

[0686] The term “cyclic group” as used herein may be a C₃-C₆₀ carbocyclic group or a C₁-C₆₀ heterocyclic group.

[0687] The term “π electron-rich C₃-C₆₀ cyclic group” as used herein may be a cyclic group that has 3 to 60 carbon atoms and may not include *—N=* as a ring-forming moiety. The term “π electron-deficient nitrogen-containing C₁-C₆₀ heterocyclic group” as used herein may be a heterocyclic group that has 1 to 60 carbon atoms and may include *—N=* as a ring-forming moiety.

[0688] In an embodiment,

[0689] a C_3 - C_{60} carbocyclic group may be a T_1 group or a group in which two or more T_1 groups are condensed with each other (e.g., a cyclopentadiene group, an adamantane group, a norbornane group, a benzene group, a pentalene group, a naphthalene group, an azulene group, an indacene group, an acenaphthylene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a perylene group, a pentaphene group, a heptalene group, a naphthacene group, a picene group, a hexacene group, a pentacene group, a rubicene group, a coronene group, an ovalene group, an indene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, an indenophenanthrene group, or an indenanthracene group),

[0690] a C_1 - C_{60} heterocyclic group may be a T_2 group, a group in which two or more T_2 groups are condensed with each other, or a group in which at least one T_2 group and at least one T_1 group are condensed with each other (e.g., a pyrrole group, a thiophene group, a furan group, an indole group, a benzindole group, a naphthoindole group, an isoindole group, a benzoisoindole group, a naphthoisoindole group, a benzosilole group, a benzothiophene group, a benzofuran group, a carbazole group, a dibenzosilole group, a dibenzothiophene group, a dibenzofuran group, an indenocarbazole group, an indolocarbazole group, a benzofurocarbazole group, a benzothienocarbazole group, a benzosilolocarbazole group, a benzindolocarbazole group, a benzocarbazole group, a benzonaphthofuran group, a benzonaphthothiophene group, a benzonaphthosilole group, a benzofurodibenzofuran group, a benzofurodibenzothiophene group, a benzothienodibenzothiophene group, a pyrazole group, an imidazole group, a triazole group, an oxazole group, an isoxazole group, an oxadiazole group, a thiazole group, an isothiazole group, a thiadiazole group, a benzopyrazole group, a benzimidazole group, a benzoxazole group, a benzoisoxazole group, a benzothiazole group, a benzoisothiazole group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a benzoisoquinoline group, a quinoxaline group, a benzoquinoxaline group, a quinazoline group, a benzoquinazoline group, a phenanthroline group, a cinnoline group, a phthalazine group, a naphthyridine group, an imidazopyridine group, an imidazopyrimidine group, an imidazotriazine group, an imidazopyrazine group, an imidazopyridazine group, an azacarbazole group, an azafluorene group, an azadibenzosilole group, an azadibenzothiophene group, an azadibenzofuran group, etc.),

[0691] a Ir electron-rich C_3 - C_{60} cyclic group may be a T_1 group, a group in which two or more T_1 groups are condensed with each other, a T_3 group, a group in which two or more T_3 groups are condensed with each other, or a group in which at least one T_3 group and at least one T_1 group are condensed with each other (e.g., a C_3 - C_{60} carbocyclic group, a 1H-pyrrole group, a silole group, a borole group, a 2H-pyrrole group, a 3H-pyrrole group, a thiophene group, a furan group, an indole group, a benzindole group, a naphthoindole group, an isoindole group, a benzoisoindole group, a naphthoisoindole group, a benzosilole group, a benzothiophene group, a benzofuran group, a carbazole group, a dibenzosilole group, a dibenzothiophene group, a dibenzofuran group, an indenocarbazole group, an indolocarbazole group, a benzofurocarbazole group, a benzoth-

ienocarbazole group, a benzosilolocarbazole group, a benzindolocarbazole group, a benzocarbazole group, a benzonaphthofuran group, a benzonaphthothiophene group, a benzonaphthosilole group, a benzofurodibenzofuran group, a benzofurodibenzothiophene group, a benzothienodibenzothiophene group, etc.),

[0692] a π electron-deficient nitrogen-containing C_1 - C_{60} heterocyclic group may be a T_4 group, a group in which two or more of T_4 groups are condensed with each other, a group in which at least one T_4 group and at least one T_1 group are condensed with each other, a group in which at least one T_4 group and at least one T_3 group are condensed with each other, or a group in which at least one T_4 group, at least one T_1 group, and at least one T_3 group are condensed with one another (e.g., a pyrazole group, an imidazole group, a triazole group, an oxazole group, an isoxazole group, an oxadiazole group, a thiazole group, an isothiazole group, a thiadiazole group, a benzopyrazole group, a benzimidazole group, a benzoxazole group, a benzoisoxazole group, a benzothiazole group, a benzoisothiazole group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a benzoisoquinoline group, a quinoxaline group, a benzoquinoxaline group, a quinazoline group, a benzoquinazoline group, a phenanthroline group, a cinnoline group, a phthalazine group, a naphthyridine group, an imidazopyridine group, an imidazopyrimidine group, an imidazotriazine group, an imidazopyrazine group, an imidazopyridazine group, an azacarbazole group, an azafluorene group, an azadibenzosilole group, an azadibenzothiophene group, an azadibenzofuran group, etc.),

[0693] wherein the T_1 group may be a cyclopropane group, a cyclobutane group, a cyclopentane group, a cyclohexane group, a cycloheptane group, a cyclooctane group, a cyclobutene group, a cyclopentene group, a cyclopentadiene group, a cyclohexene group, a cyclohexadiene group, a cycloheptene group, an adamantane group, a norbornane (or bicyclo[2.2.1] heptane) group, a norbornene group, a bicyclo[1.1.1] pentane group, a bicyclo[2.1.1] hexane group, a bicyclo[2.2.2] octane group, or a benzene group,

[0694] the T_2 group may be a furan group, a thiophene group, a 1H-pyrrole group, a silole group, a borole group, a 2H-pyrrole group, a 3H-pyrrole group, an imidazole group, a pyrazole group, a triazole group, a tetrazole group, an oxazole group, an isoxazole group, an oxadiazole group, a thiazole group, an isothiazole group, a thiadiazole group, an azasilole group, an azaborole group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, a tetrazine group, a pyrrolidine group, an imidazolidine group, a dihydropyrrole group, a piperidine group, a tetrahydropyridine group, a dihydropyrimidine group, a hexahydropyrimidine group, a tetrahydropyrimidine group, a dihydropyrimidine group, a piperazine group, a tetrahydropyrazine group, a dihydropyrazine group, a tetrahydropyridazine group, or a dihydropyridazine group,

[0695] the T_3 group may be a furan group, a thiophene group, a 1H-pyrrole group, a silole group, or a borole group, and

[0696] the T_4 group may be a 2H-pyrrole group, a 3H-pyrrole group, an imidazole group, a pyrazole group, a triazole group, a tetrazole group, an oxazole group, an isoxazole group, an oxadiazole group, a thiazole group, an isothiazole group, a thiadiazole group, an azasilole group, an azaborole

group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, or a tetrazine group.

[0697] The terms “cyclic group”, “C₃-C₆₀ carbocyclic group”, “C₁-C₆₀ heterocyclic group”, “π electron-rich C₃-C₆₀ cyclic group”, and “π electron-deficient nitrogen-containing C₁-C₆₀ heterocyclic group” as used herein may each be a group condensed to any cyclic group, a monovalent group, or a polyvalent group (e.g., a divalent group, a trivalent group, a tetravalent group, etc.) according to the structure of a formula for which the corresponding term is used. For example, a “benzene group” may be a benzo group, a phenyl group, a phenylene group, or the like, which may be readily understood by those of ordinary skill in the art according to the structure of a formula including the “benzene group”.

[0698] Examples of a monovalent C₃-C₆₀ carbocyclic group or a monovalent C₁-C₆₀ heterocyclic group may include a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₅-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group. Examples of a divalent C₃-C₆₀ carbocyclic group or a divalent C₁-C₆₀ heterocyclic group may include a C₃-C₁₀ cycloalkylene group, a C₁-C₁₀ heterocycloalkylene group, a C₅-C₁₀ cycloalkenylene group, a C₁-C₁₀ heterocycloalkenylene group, a C₆-C₆₀ arylene group, a C₁-C₆₀ heteroarylene group, a divalent non-aromatic condensed polycyclic group, and a divalent non-aromatic condensed heteropolycyclic group.

[0699] The term “C₁-C₆₀ alkyl group” as used herein may be a linear or branched monovalent aliphatic hydrocarbon group that has 1 to 60 carbon atoms, and examples thereof may include a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, and the like. The term “C₁-C₆₀ alkylene group” as used herein may be a divalent group having a same structure as the C₁-C₆₀ alkyl group.

[0700] The term “C₂-C₆₀ alkenyl group” as used herein may be a monovalent hydrocarbon group having at least one carbon-carbon double bond in the middle or at a terminus of a C₂-C₆₀ alkyl group, and examples thereof may include an ethenyl group, a propenyl group, a butenyl group, and the like. The term “C₂-C₆₀ alkenylene group” as used herein may be a divalent group having a same structure as the C₂-C₆₀ alkenyl group.

[0701] The term “C₂-C₆₀ alkynyl group” as used herein may be a monovalent hydrocarbon group having at least one carbon-carbon triple bond in the middle or at a terminus of a C₂-C₆₀ alkyl group, and examples thereof may include an ethynyl group, a propynyl group, and the like. The term “C₂-C₆₀ alkynylene group” as used herein may be a divalent group having a same structure as the C₂-C₆₀ alkynyl group.

[0702] The term “C₁-C₆₀ alkoxy group” as used herein may be a monovalent group represented by —O(A₁₀₁) (wherein A₁₀₁ may be a C₁-C₆₀ alkyl group), and examples thereof may include a methoxy group, an ethoxy group, an isopropoxy group, and the like.

[0703] The term “C₃-C₁₀ cycloalkyl group” as used herein may be a monovalent saturated hydrocarbon cyclic group having 3 to 10 carbon atoms, and examples thereof may include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group (or bicyclo[2.2.1] heptyl group), a bicyclo[1.1.1] pentyl group, a bicyclo[2.1.1] hexyl group, a bicyclo[2.2.2] octyl group, and the like. The term “C₃-C₁₀ cycloalkylene group” as used herein may be a divalent group having a same structure as the C₃-C₁₀ cycloalkyl group.

[0704] The term “C₁-C₁₀ heterocycloalkyl group” as used herein may be a monovalent cyclic group having 1 to 10 carbon atoms, further including, in addition to carbon atoms, at least one heteroatom as ring-forming atoms, and examples thereof may include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuranyl group, a tetrahydrothiophenyl group, and the like. The term “C₁-C₁₀ heterocycloalkylene group” as used herein may be a divalent group having a same structure as the C₁-C₁₀ heterocycloalkyl group.

[0705] The term “C₃-C₁₀ cycloalkenyl group” as used herein may be a monovalent cyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the cyclic structure thereof and no aromaticity, and examples thereof may include a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, and the like. The term “C₃-C₁₀ cycloalkenylene group” as used herein may be a divalent group having a same structure as the C₃-C₁₀ cycloalkenyl group.

[0706] The term “C₁-C₁₀ heterocycloalkenyl group” as used herein may be a monovalent cyclic group that has 1 to 10 carbon atoms, further including, in addition to carbon atoms, at least one heteroatom as ring-forming atoms, and having at least one carbon-carbon double bond in the cyclic structure thereof. Examples of a C₁-C₁₀ heterocycloalkenyl group may include a 4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-dihydrofuranyl group, a 2,3-dihydrothiophenyl group, and the like. The term “C₁-C₁₀ heterocycloalkenylene group” as used herein may be a divalent group having a same structure as the C₁-C₁₀ heterocycloalkenyl group.

[0707] The term “C₆-C₆₀ aryl group” as used herein may be a monovalent group having a carbocyclic aromatic system of 6 to 60 carbon atoms, and the term “C₆-C₆₀ arylene group” as used herein may be a divalent group having a carbocyclic aromatic system of 6 to 60 carbon atoms. Examples of a C₆-C₆₀ aryl group may include a phenyl group, a pentalenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a heptalenyl group, a naphthacenyl group, a picenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, and the like. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the respective two or more rings may be condensed with each other.

[0708] The term “C₁-C₆₀ heteroaryl group” as used herein may be a monovalent group having a heterocyclic aromatic

system of 1 to 60 carbon atoms, further including, in addition to carbon atoms, at least one heteroatom as ring-forming atoms. The term “C₁-C₆₀ heteroarylene group” as used herein may be a divalent group having a heterocyclic aromatic system of 1 to 60 carbon atoms, further including, in addition to carbon atoms, at least one heteroatom as ring-forming atoms. Examples of a C₁-C₆₀ heteroaryl group may include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a benzoisoquinolinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthrolinyl group, a phthalazinyl group, a naphthyridinyl group, and the like. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the respective two or more rings may be condensed with each other.

[0709] The term “monovalent non-aromatic condensed polycyclic group” as used herein may be a monovalent group (e.g., having 8 to 60 carbon atoms) having two or more rings condensed to each other, only carbon atoms as ring-forming atoms, and no aromaticity in its molecular structure as a whole. Examples of a monovalent non-aromatic condensed polycyclic group may include an indenyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, an indenophenanthrenyl group, an indenoanthracenyl group, and the like. The term “divalent non-aromatic condensed polycyclic group” as used herein may be a divalent group having a same structure as the monovalent non-aromatic condensed polycyclic group.

[0710] The term “monovalent non-aromatic condensed heteropolycyclic group” as used herein may be a monovalent group (e.g., having 1 to 60 carbon atoms) having two or more rings condensed to each other, further including, in addition to carbon atoms, at least one heteroatom as ring-forming atoms, and having no aromaticity in its molecular structure as a whole. Examples of a monovalent non-aromatic condensed heteropolycyclic group may include a pyrrolyl group, a thiophenyl group, a furanyl group, an indolyl group, a benzoindolyl group, a naphthoindolyl group, an isoindolyl group, a benzoisoindolyl group, a naphthoisoindolyl group, a benzosilolyl group, a benzothio-phenyl group, a benzofuranyl group, a carbazolyl group, a dibenzosilolyl group, a dibenzothio-phenyl group, a dibenzofuranyl group, an azacarbazolyl group, an azafuorenyl group, an azadibenzosilolyl group, an azadibenzothio-phenyl group, an azadibenzofuranyl group, a pyrazolyl group, an imidazolyl group, a triazolyl group, a tetrazolyl group, an oxazolyl group, an isoxazolyl group, a thiazolyl group, an isothiazolyl group, an oxadiazolyl group, a thiadiazolyl group, a benzopyrazolyl group, a benzimidazolyl group, a benzoxazolyl group, a benzothiazolyl group, a benzoxadiazolyl group, a benzothiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an imidazotriazinyl group, an imidazopyrazinyl group, an imidazopyridazinyl group, an indenocarbazolyl group, an indolocarbazolyl group, a benzofurocarbazolyl group, a benzothienocarbazolyl group, a benzosilolocarbazolyl group, a benzoindolocarbazolyl group, a benzocarbazolyl group, a benzonaphthofuranyl group, a benzonaphthothio-phenyl group, a benzonaphthosilolyl group, a benzofurodibenzofuranyl group, a benzofurodibenzothio-phenyl group, a benzothienodibenzothio-phenyl group, and the like. The term

“divalent non-aromatic condensed heteropolycyclic group” as used herein may be a divalent group having a same structure as the monovalent non-aromatic condensed heteropolycyclic group.

[0711] The term “C₆-C₆₀ aryloxy group” as used herein may be a group represented by —O(A₁₀₂) (wherein A₁₀₂ may be a C₆-C₆₀ aryl group), and the term “C₆-C₆₀ arylthio group” as used herein may be a group represented by —S(A₁₀₃) (wherein A₁₀₃ may be a C₆-C₆₀ aryl group).

[0712] The term “C₇-C₆₀ arylalkyl group” as used herein may be a group represented by —(A₁₀₄)(A₁₀₅) (wherein A₁₀₄ may be a C₁-C₅₄ alkylene group, and A₁₀₅ may be a C₆-C₅₉ aryl group), and the term “C₂-C₆₀ heteroarylalkyl group” as used herein may be a group represented by —(A₁₀₆)(A₁₀₇) (wherein A₁₀₆ may be a C₁-C₅₉ alkylene group, and A₁₀₇ may be a C₁-C₅₉ heteroaryl group).

[0713] In the specification, the group “R_{10a}” may be:

[0714] deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, or a nitro group;

[0715] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₃-C₆₀ carbocyclic group, a C₁-C₆₀ heterocyclic group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₂-C₆₀ heteroarylalkyl group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), —P(=O)(Q₁₁)(Q₁₂), or any combination thereof;

[0716] a C₃-C₆₀ carbocyclic group, a C₁-C₆₀ heterocyclic group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, or a C₂-C₆₀ heteroarylalkyl group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₆₀ carbocyclic group, a C₁-C₆₀ heterocyclic group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₂-C₆₀ heteroarylalkyl group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), —P(=O)(Q₂₁)(Q₂₂), or any combination thereof; or

[0717] —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), or —P(=O)(Q₃₁)(Q₃₂).

[0718] In the specification, the groups Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ may each independently be: hydrogen; deuterium; —F; —Cl; —Br; —I; a hydroxyl group; a cyano group; a nitro group; a C₁-C₆₀ alkyl group; a C₂-C₆₀ alkenyl group; a C₂-C₆₀ alkynyl group; a C₁-C₆₀ alkoxy group; a C₃-C₆₀ carbocyclic group or a C₁-C₆₀ heterocyclic group, each unsubstituted or substituted with deuterium, —F, a cyano group, a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a biphenyl group, or any combination thereof; a C₇-C₆₀ arylalkyl group; or a C₂-C₆₀ heteroarylalkyl group.

[0719] The term “heteroatom” as used herein may be any atom other than a carbon atom or a hydrogen atom. Examples of a heteroatom may include O, S, N, P, Si, B, Ge, Se, and any combination thereof.

[0720] In the specification, examples of a “third-row transition metal” may include hafnium (Hf), tantalum (Ta),

tungsten (W), rhenium (Re), osmium (Os), iridium (Ir), platinum (Pt), gold (Au), and the like.

[0721] In the specification, the term “Ph” refers to a phenyl group, the term “Me” refers to a methyl group, the term “Et” refers to an ethyl group, the terms “ter-Bu” and “But” each refer to a tert-butyl group, and the term “OMe” refers to a methoxy group.

[0722] The term “biphenyl group” as used herein may be a “phenyl group substituted with a phenyl group.” For example, a “biphenyl group” may be a substituted phenyl group having a C₆-C₆₀ aryl group as a substituent.

[0723] The term “terphenyl group” as used herein may be a “phenyl group substituted with a biphenyl group.” For example, a “terphenyl group” may be a substituted phenyl group having, as a substituent, a C₆-C₆₀ aryl group substituted with a C₆-C₆₀ aryl group.

[0724] In the specification, the symbols * and *, unless defined otherwise, each refer to a binding site to a neighboring atom in a corresponding formula or moiety.

[0725] In the specification, the terms “x-axis”, “y-axis”, and “z-axis” are not limited to three axes in an orthogonal coordinate system (e.g., a Cartesian coordinate system), and may be interpreted in a broader sense than the aforementioned three axes in an orthogonal coordinate system. For example, the x-axis, y-axis, and z-axis may describe axes that are orthogonal to each other, or may describe axes that are in different directions that are not orthogonal to each other.

[0726] Hereinafter, compounds according to embodiments and light-emitting devices according to embodiments will be described in detail with reference to the Synthesis Examples and the Examples. The wording “B was used instead of A” used in describing Synthesis Examples means that an identical molar equivalent of B was used in place of A.

Synthesis Examples and Examples

Synthesis Example 1: Synthesis of Compound 1

[0727] n-BuLi (1.6 M, 12.8 mL, 20.5 mmol) was added dropwise at -78° C. to a solution of 1,3-bis(2-(3-bromophenyl)propan-2-yl)benzene (4.72 g, 10.0 mmol) dissolved in anhydrous THF (100 mL). After the resultant solution was stirred for 1 hour, while stirring at -78° C., 10-phenylacridin-9 (10H)-one (2.98 g, 11.0 mmol) in a powder form was added thereto. The temperature was raised to room temperature, and the resultant reaction mixture was stirred for 3 hours. After quenching with a small amount of water, the resultant mixture was concentrated, and diluted with CH₂Cl₂ (300 mL). The resultant solution was washed with water, and an aqueous phase was extracted twice therefrom with CH₂Cl₂. A CH₂Cl₂ solution thus collected was dried with Na₂SO₄, and concentrated to obtain a hydroxy intermediate. The crude hydroxy intermediate was diluted with CH₂Cl₂ (200 mL), methanesulfonic acid (0.96 g, 10.0 mmol) was added thereto, and refluxed for 2 hours. After cooling to room temperature, the resultant solution was poured into an excess amount of aqueous NaHCO₃ solution. The resultant product was subjected to an extraction process with CH₂Cl₂, and dried with Na₂SO₄. After filtration and evaporation, the resultant crude product was purified by silica gel column chromatography, and dried under reduced pressure to obtain Intermediate 1a in a solid form.

[0728] Boron triiodide (1.85 g, 4.7 mmol) was added to Intermediate 1a (2.44 g, 4.3 mmol) dissolved in anhydrous

o-dichlorobenzene, and stirred at 140° C. for 24 hours. An excess amount of CH₂Cl₂ was added to the resultant mixture at room temperature, and stirred for 1 hour. After adding water, the resultant product was subjected to an extraction process with CH₂Cl₂. An organic layer thus collected was washed with brine, and dried with anhydrous Na₂SO₄. After filtration and evaporation, the resultant crude product was purified by silica gel column chromatography. After removing the solvent by evaporation, the resultant solid was washed with MeOH to obtain Compound 1 in a solid form (yield=0.69 g, 28%).

Synthesis Example 2: Synthesis of Compound 2

[0729] At 0° C. under N₂, n-BuLi (1.6 M, 13.1 mL, 21.0 mmol) dissolved in hexane was added dropwise to a solution obtained by mixing and stirring 2-bromo-N-(2-g, bromophenyl)-N-phenylaniline (4.03 g, 10.0 mmol) and 1,3-bis(2-(3-bromophenyl)propan-2-yl)benzene (4.72 g, 10.0 mmol) dissolved in anhydrous diethyl ether (100 mL). After the resultant mixture was stirred at 0° C. for 1 hour, tetrachlorosilane (1.90 g, 11.2 mmol) was added dropwise thereto. The resultant reaction mixture was stirred at 35° C. for 2 hours, and cooled to room temperature. After adding water, the resultant product was subjected to an extraction process with AcOEt. An organic layer thus collected was washed with brine, and dried with anhydrous Na₂SO₄. After filtration and evaporation, the resultant crude product was purified by silica gel column chromatography. After removing the solvent by evaporation, the resultant solid was washed with MeOH to obtain Intermediate 2a as a solid.

[0730] Boron triiodide (2.66 g, 6.8 mmol) was added to Intermediate 2a (3.62 g, 6.2 mmol) dissolved in anhydrous o-dichlorobenzene, and stirred at 140° C. for 24 hours. An excess amount of CH₂Cl₂ was added to the resultant mixture at room temperature, and stirred for 1 hour. After adding water, the resultant product was subjected to an extraction process with CH₂Cl₂. An organic layer thus collected was washed with brine, and dried with anhydrous Na₂SO₄. After filtration and evaporation, the resultant crude product was purified by silica gel column chromatography. After removing the solvent by evaporation, the resultant solid was washed with MeOH to obtain Compound 2 in a solid form (yield=2.97 g, 50%).

Synthesis Example 3: Synthesis of Compound 3

[0731] Compound 3 was synthesized in the same manner as in the synthesis of Compound 2, except that tetrachlorogermane (2.40 g, 11.2 mmol) was used instead of tetrachlorosilane (yield=2.16 g, 34%).

Synthesis Example 4: Synthesis of Compound 4

[0732] n-BuLi (1.6 M, 12.8 mL, 20.5 mmol) was added dropwise at -78° C. to a solution of 1,3-bis(9-(3-bromophenyl)-9H-fluoren-9-yl)benzene (7.17 g, 10.0 mmol) dissolved in anhydrous THF (100 mL). After the resultant solution was stirred for 1 hour, while stirring at -78° C., 10-([1,1':3',1'-terphenyl]-2'-yl)acridin-9 (10H)-one (4.66 g, 11.0 mmol) in a powder form was added thereto. The temperature was raised to room temperature, and the resultant reaction mixture was stirred for 3 hours. After quenching with a small amount of water, the resultant mixture was concentrated, and diluted with CH₂Cl₂ (300 mL). The resultant solution was washed with water, and an aqueous phase was extracted

twice therefrom with CH_2Cl_2 . A CH_2Cl_2 solution thus collected was dried with Na_2SO_4 , and concentrated to obtain a hydroxy intermediate. The crude hydroxy intermediate was

compound synthesized in Synthesis Examples may be readily recognized by those skilled in the art by referring to the synthesis paths and source materials.

TABLE 1

Compound No.	MS/FAB		¹ H NMR Elemental Analysis	
	found	calc.	found	calc.
1	575.39	575.28	C, 89.75; H, 6.01; N, 2.48	C, 89.73; H, 5.95; N, 2.43
2	591.35	591.26	C, 85.31; H, 5.89; N, 2.40	C, 85.27; H, 5.79; N, 2.37
3	637.30	637.20	C, 79.35; H, 5.49; N, 2.21	C, 79.30; H, 5.39; N, 2.20
4	971.46	971.37	C, 92.70; H, 4.88; N, 1.46	C, 92.68; H, 4.77; N, 1.44
5	987.45	987.35	C, 89.98; H, 4.78; N, 1.43	C, 89.95; H, 4.69; N, 1.42
6	1033.41	1033.29	C, 86.10; H, 4.60; N, 1.37	C, 86.07; H, 4.49; N, 1.36

diluted with CH_2Cl_2 (200 mL), methanesulfonic acid (0.96 g, 10.0 mmol) was added thereto, and refluxed for 2 hours. After cooling to room temperature, the resultant solution was carefully poured into an excess amount of aqueous NaHCO_3 solution. The resultant product was subjected to an extraction process with CH_2Cl_2 , and dried with Na_2SO_4 . After filtration and evaporation, the resultant crude product was purified by silica gel column chromatography, and dried under reduced pressure to obtain Intermediate **4a** in a solid form.

[0733] Boron triiodide (1.25 g, 3.2 mmol) was added to Intermediate **4a** (2.80 g, 2.9 mmol) dissolved in anhydrous o-dichlorobenzene, and stirred at 140° C. for 24 hours. An excess amount of CH_2Cl_2 was added to the resultant mixture at room temperature, and stirred for 1 hour. After adding water, the resultant product was subjected to an extraction process with CH_2Cl_2 . An organic layer thus collected was washed with brine, and dried with anhydrous Na_2SO_4 . After filtration and evaporation, the resultant crude product was purified by silica gel column chromatography. After removing the solvent by evaporation, the resultant solid was washed with MeOH to obtain Compound 4 in a solid form (yield=2.37 g, 24%).

Synthesis Example 5: Synthesis of Compound 5

[0734] Compound 5 was synthesized in the same manner as in the synthesis of Compound 2, except that N,N-bis(2-bromophenyl)-[1,1': 3',1"-terphenyl]-2'-amine (5.55 g, 10.0 mmol) was used instead of 2-bromo-N-(2-bromophenyl)-N-phenylaniline, and 1,3-bis(9-(3-bromophenyl)-9H-fluoren-9-yl)benzene (7.17 g, 10.0 mmol) was used instead of 1,3-bis(2-(3-bromophenyl) propan-2-yl)benzene (yield=3.06 g, 31%).

Synthesis Example 6: Synthesis of Compound 6

[0735] Compound 6 was synthesized in the same manner as in the synthesis of Compound 2, except that N,N-bis(2-bromophenyl)-[1,1': 3',1"-terphenyl]-2'-amine (5.55 g, 10.0 mmol) was used instead of 2-bromo-N-(2-bromophenyl)-N-phenylaniline, 1,3-bis(9-(3-bromophenyl)-9H-fluoren-9-yl)benzene (7.17 g, 10.0 mmol) was used instead of 1,3-bis(2-(3-bromophenyl) propan-2-yl)benzene, and tetrachlorogermane (2.40 g, 11.2 mmol) was used instead of tetrachlorosilane (yield=1.96 g, 19%).

[0736] ¹H NMR and MS/FAB of the compounds synthesized according to Synthesis Examples are shown in Table 1. Synthesis methods of other compounds in addition to the

Evaluation Example 1

[0737] The HOMO energy level (E_{HOMO}), LUMO energy level (E_{LUMO}), HOMO-LUMO band gap energy (E_g), T_1 energy level (nm), and existence ratio (%) of a triplet metal-to-ligand charge transfer state (³MLCT) of Compounds 1 to 6 were evaluated using the density functional theory (DFT) method of the Gaussian program, which was structure-optimized at the B3LYP/6-311G (d,p) level, and results thereof are shown in Table 2.

TABLE 2

Compound No.	E_{HOMO} (eV)	E_{LUMO} (eV)	E_g (eV)	T_1 (nm)
1	-5.14	-1.82	3.32	394
2	-5.28	-1.99	3.29	423
3	-5.25	-2.00	3.25	425
4	-5.17	-1.85	3.32	408
5	-5.31	-2.02	3.29	416
6	-5.29	-2.03	3.26	418

Example 1

[0738] As an anode, a glass substrate (product of Corning Inc.) with a 15 Ω/cm^2 (1,200 Å) ITO formed thereon was cut to a size of 50 mm×50 mm×0.7 mm, sonicated by using isopropyl alcohol and pure water each for 5 minutes, washed by irradiation of ultraviolet rays and exposure of ozone thereto for 30 minutes, and mounted on a vacuum deposition apparatus.

[0739] 2-TNATA was vacuum-deposited on the anode to form a hole injection layer having a thickness of 600 Å. 4,4'-bis [N-(1-naphthyl)-N-phenylamino]biphenyl (hereinafter, referred to as NPB) was vacuum-deposited on the hole injection layer to form a hole transport layer having a thickness of 300 Å.

[0740] Compound 1, Compound DFD29, Compound HTH29, and Compound ETH2 were vacuum-deposited on the hole transport layer to form an emission layer having a thickness of 350 Å. The amount of Compound 1 was 13 parts by weight based on total 100 parts by weight of the emission layer, and the amount of Compound DFD29 was 0.4 parts by weight based on total 100 parts by weight of the emission layer. The balance of the emission layer by weight consisted of Compound HTH29 and Compound ETH2. The weight ratio of Compound HTH29 to Compound ETH2 was 6.5:3.5.

[0741] Compound HBL-1 was vacuum-deposited on the emission layer to form a hole blocking layer having a thickness of 50 Å.


[0742] CNNPTRZ and LiQ were vacuum-deposited on the hole blocking layer to form an electron transport layer having a thickness of 310 Å. The weight ratio of CNNPTRZ to LiQ was 4:6.

[0743] Yb was vacuum-deposited on the electron transport layer to form an electron injection layer having a thickness of 15 Å.


[0744] Mg was vacuum-deposited on the electron injection layer to form a cathode having a thickness of 800 Å, thereby completing the manufacture of an organic light-emitting device.

-continued


ETH2




HTH29




HBL-1




CNNPTRZ




2-TNATA



NPB





Examples 2 to 6 and Comparative Examples 1 to 3

[0745] Organic light-emitting devices were manufactured in the same manner as in Example 1, except that the compound used in forming the emission layer was changed as shown in Table 3.

Evaluation Example 1

[0746] The driving voltage (V) at 1,000 cd/m², current efficiency (cd/A), maximum emission wavelength (nm), and

lifespan (T95) of the organic light-emitting devices manufactured in Examples 1 to 6 and Comparative Examples 1 to 3 were measured using Keithley MU 236 and luminance meter PR650, and results thereof are shown in Table 3. The lifespan (T95) is a measure of the time (hr) taken until the luminance declines to 95% of the initial luminance.

[0747] In an embodiment, for the organic light-emitting devices manufactured in Examples 1 to 6 and Comparative Examples 1 to 3, the emission quantum yield (Φ_{PL}) was determined through Quantaury-QY, and the prompt (p) and delay (d) components were extracted using a streak camera to determine the exciton lifespan (T_p , T_d) and the luminescent component ratio (Φ_p , Φ_d). The RISC speed (K_{RISC}) was calculated using the following calculation formulae, and results thereof are shown in Table 3.

$$\Phi_{PL} = \Phi_p + \Phi_d$$
$$k_r = \Phi_p/T_p$$
$$k_{ISC} = (1 - \Phi_p)/T_p$$
$$k_{RISC} = \Phi_d/(k_{ISC} \cdot T_p \cdot T_d \cdot \Phi_p)$$

[0748] In Table 3, the RISC speed, current efficiency, and T95 show relative values with the values of Example 1 set to 100%.

TABLE 3

	Heterocyclic compound	RISC speed	Driving voltage (V)	Current efficiency (cd/A)	Maximum emission wavelength (nm)	Lifespan (T ₉₅ , hr)
Example 1	1	100%	4.0	100%	460	100%
Example 2	2	190%	4.0	160%	460	120%
Example 3	3	370%	4.0	220%	460	140%
Example 4	4	100%	4.1	150%	460	240%
Example 5	5	190%	4.1	230%	460	290%
Example 6	6	370%	4.1	300%	460	340%
Comparative Example 1	CE1	90%	4.2	97%	460	21%
Comparative Example 2	CE2	30%	5.0	65%	460	2%
Comparative Example 3	CE3	80%	4.0	95%	460	13%






TABLE 3-continued


Heterocyclic compound	RISC speed	Driving voltage (V)	Current efficiency (cd/A)	Maximum emission wavelength (nm)	Lifespan (T ₉₅ , hr)
-----------------------	------------	---------------------	---------------------------	----------------------------------	---------------------------------




2



3




4




5

TABLE 3-continued


Heterocyclic compound	RISC speed	Driving voltage (V)	Current efficiency (cd/A)	Maximum emission wavelength (nm)	Lifespan (T ₉₅ , hr)
--------------------------	---------------	---------------------------	---------------------------------	--	------------------------------------



6




CE1



CE2

TABLE 3-continued

Heterocyclic compound	RISC speed	Driving voltage (V)	Current efficiency (cd/A)	Maximum emission wavelength (nm)	Lifespan (T ₉₅ , hr)
					
CE3					

[0749] Referring to Table 3, it was confirmed that the organic light-emitting devices according to Examples 1 to 6 emitted blue light and had superior RISC speed, luminescence efficiency, and device lifespan compared to the organic light-emitting devices according to Comparative Examples 1 to 3.

[0750] According to the embodiments, by using a heterocyclic compound, a light-emitting device having reduced driving voltage, improved color purity and efficiency, and increased lifespan, and a high-quality electronic apparatus including the light-emitting device may be manufactured.

[0751] Embodiments have been disclosed herein, and although terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purposes of limitation. In some instances, as would be apparent by one of ordinary skill in the art, features, characteristics, and/or elements described in connection with an embodiment may be used singly or in combination with features, characteristics, and/or elements described in connection with other embodiments unless otherwise specifically indicated. Accordingly, it will be understood by those of ordinary skill in the art that various changes in form and details may be made without departing from the spirit and scope of the disclosure

What is claimed is:

1. A light-emitting device comprising:

a first electrode;

a second electrode facing the first electrode;

an interlayer between the first electrode and the second electrode and including an emission layer; and

a heterocyclic compound including:

an electron donor moiety including nitrogen;

an electron acceptor moiety including boron; and

a spiro core atom, wherein

the spiro core atom is bonded to the electron donor moiety via a first bond and a second bond,

the spiro core atom is bonded to the electron acceptor moiety via a third bond and a fourth bond,

the first bond, the second bond, the third bond, and the fourth bond are each a single bond, and

at least one of Conditions 1 to 3 is satisfied:

[Condition 1]

the electron donor moiety includes a group represented by Formula 1A;

[Condition 2]


the electron acceptor moiety includes a first ring, a second ring, and a third ring each bonded to the boron, the first ring and the third ring are bonded to the spiro core

atom, and the first ring and the second ring are linked to each other via a first linking group;

[Condition 3]

the electron acceptor moiety includes a first ring, a second ring, and a third ring each bonded to the boron, the first ring and the third ring are bonded to the spiro core atom, and the second ring and the third ring are linked to each other via a second linking group;

[Formula 1A]



wherein in Formula 1A,

R₆₁ to R₆₃ are each independently hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₆₀ alkyl group unsubstituted or substituted with at least one R_{10a}, a C₂-C₆₀ alkenyl group unsubstituted or substituted with at least one R_{10a}, a C₂-C₆₀ alkynyl group unsubstituted or substituted with at least one R_{10a}, a C₁-C₆₀ alkoxy group unsubstituted or substituted with at least one R_{10a}, a C₁-C₆₀ alkylthio group unsubstituted or substituted with at least one R_{10a}, a C₃-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{10a}, a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a}, a C₆-C₆₀ aryloxy group unsubstituted or substituted with at least one R_{10a}, a C₆-C₆₀ arylthio group unsubstituted or substituted with at least one R_{10a}, —C(Q₁)(Q₂)(Q₃), —Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)₂(Q₁), or —P(=O)(Q₁)(Q₂),

a₆₁ and a₆₃ are each independently an integer from 1 to 5,

a₆₂ is an integer from 1 to 3,

* indicates a binding site to a neighboring atom,


R_{10a} is:

hydrogen, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, or a nitro group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group, each unsub-

- stituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₅-C₆₀ carbocyclic group, a C₁-C₆₀ heterocyclic group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), —P(=O)(Q₁₁)(Q₁₂), or a combination thereof;
- a C₃-C₆₀ carbocyclic group, a C₁-C₆₀ heterocyclic group, a C₆-C₆₀ aryloxy group, or a C₆-C₆₀ arylthio group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₆₀ carbocyclic group, a C₁-C₆₀ heterocyclic group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), —P(=O)(Q₂₁)(Q₂₂), or a combination thereof; or —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), or —P(=O)(Q₃₁)(Q₃₂), and Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ are each independently:
- hydrogen; deuterium; —F; —Cl; —Br; —I; a hydroxyl group; a cyano group; a nitro group; a C₁-C₆₀ alkyl group; a C₂-C₆₀ alkenyl group; a C₂-C₆₀ alkynyl group; a C₁-C₆₀ alkoxy group; or a C₃-C₆₀ carbocyclic group or a C₁-C₆₀ heterocyclic group, each unsubstituted or substituted with deuterium, —F, a cyano group, a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a biphenyl group, or a combination thereof.
2. The light-emitting device of claim 1, wherein the emission layer includes a host and a dopant, and the dopant includes the heterocyclic compound.
3. The light-emitting device of claim 1, further comprising:
- a second compound including at least one π electron-deficient nitrogen-containing C₁-C₆₀ heterocyclic group; or
 - a third compound including a group represented by Formula 3; or
 - a fourth compound that emits delayed fluorescence; or
 - a combination thereof, wherein the heterocyclic compound, the second compound, the third compound, and the fourth compound are different from each other;

[Formula 3]




wherein in Formula 3, ring CY₇₁ and ring CY₇₂ are each independently a Ir electron-rich C₃-C₆₀ cyclic group or a pyridine group, X₇₁ is: a single bond; or a linking group including O, S, N, B, C, Si, or a combination thereof, and * indicates a binding site to any atom included in a remaining part of the third compound other than the group represented by Formula 3.

4. The light-emitting device of claim 3, wherein the second compound includes a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, or a combination thereof, and the fourth compound is a compound including at least one cyclic group including both boron (B) and nitrogen (N) as ring-forming atoms.
5. The light-emitting device of claim 3, wherein the emission layer includes:
- the heterocyclic compound; and
 - the second compound, the third compound, the fourth compound, or a combination thereof, and the emission layer emits blue light.
6. An electronic apparatus comprising the light-emitting device of claim 1.
7. The electronic apparatus of claim 6, further comprising: a thin-film transistor, wherein the thin-film transistor includes a source electrode and a drain electrode, and the first electrode of the light-emitting device is electrically connected to at least one of the source electrode and the drain electrode.
8. The electronic apparatus of claim 6, further comprising: a color filter, a color conversion layer, a touch screen layer, a polarizing layer, or a combination thereof.
9. An electronic equipment comprising the light-emitting device of claim 1.
10. The electronic equipment of claim 9, wherein the electronic equipment is a flat panel display, a curved display, a computer monitor, a medical monitor, a television, a billboard, an indoor light, an outdoor light, a signal light, a head-up display, a fully transparent display, a partially transparent display, a flexible display, a rollable display, a foldable display, a stretchable display, a laser printer, a telephone, a mobile phone, a tablet computer, a phablet, a personal digital assistant (PDA), a wearable device, a laptop computer, a digital camera, a camcorder, a viewfinder, a micro display, a three-dimensional (3D) display, a virtual reality display, an augmented reality display, a vehicle, a video wall with multiple displays tiled together, a theater screen, a stadium screen, a phototherapy device, or a sign-board.
11. A heterocyclic compound comprising:
- an electron donor moiety including nitrogen;
 - an electron acceptor moiety including boron; and
 - a spiro core atom, wherein the spiro core atom is bonded to the electron donor moiety via a first bond and a second bond, the spiro core atom is bonded to the electron acceptor moiety via a third bond and a fourth bond, the first bond, the second bond, the third bond, and the fourth bond are each a single bond, and at least one of Conditions 1 to 3 is satisfied:
- [Condition 1]
the electron donor moiety includes a group represented by Formula 1A;
- [Condition 2]
the electron acceptor moiety includes a first ring, a second ring, and a third ring each bonded to the boron, the first ring and the third ring are bonded to the spiro core atom, and the first ring and the second ring are linked to each other via a first linking group;

[Condition 3]

the electron acceptor moiety includes a first ring, a second ring, and a third ring each bonded to the boron, the first ring and the third ring are bonded to the spiro core atom, and the second ring and the third ring are linked to each other via a second linking group;

[Formula 1A]



wherein in Formula 1A,

R_{61} to R_{63} are each independently hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{60} alkyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkenyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkynyl group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkoxy group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkylthio group unsubstituted or substituted with at least one R_{10a} , a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} aryloxy group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} arylthio group unsubstituted or substituted with at least one R_{10a} , —C(Q_1)(Q_2)(Q_3), —Si(Q_1)(Q_2)(Q_3), —N(Q_1)(Q_2), —B(Q_1)(Q_2), —C(=O)(Q_1), —S(=O)₂(Q_1), or —P(=O)(Q_1)(Q_2),

a_{61} and a_{63} are each independently an integer from 1 to 5,

a_{62} is an integer from 1 to 3,

* indicates a binding site to a neighboring atom,

R_{10a} is:

hydrogen, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, or a nitro group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, or a C_1 - C_{60} alkoxy group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C_3 - C_{60} carbocyclic group, a C_1 - C_{60} heterocyclic group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, —Si(Q_{11})(Q_{12})(Q_{13}), —N(Q_{11})(Q_{12}), —B(Q_{11})(Q_{12}), —C(=O)(Q_{11}), —S(=O)₂(Q_{11}), —P(=O)(Q_{11})(Q_{12}), or a combination thereof;


a C_5 - C_{60} carbocyclic group, a C_1 - C_{60} heterocyclic group, a C_6 - C_{60} aryloxy group, or a C_6 - C_{60} arylthio group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_5 - C_{60} carbocyclic group, a C_1 - C_{60} heterocyclic group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, —Si(Q_{21})(Q_{22})(Q_{23}), —N(Q_{21})(Q_{22}), —B(Q_{21})(Q_{22}), —C(=O)(Q_{21}), —S(=O)₂(Q_{21}), —P(=O)(Q_{21})(Q_{22}), or a combination thereof; or

—Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), or —P(=O)(Q_{31})(Q_{32}), and

Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} are each independently: hydrogen; deuterium; —F; —Cl; —Br; —I; a hydroxyl group; a cyano group; a nitro group; a C_1 - C_{60} alkyl group; a C_2 - C_{60} alkenyl group; a C_2 - C_{60} alkynyl group; a C_1 - C_{60} alkoxy group; or a C_3 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group, each unsubstituted or substituted with deuterium, —F, a cyano group, a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a biphenyl group, or a combination thereof.

12. The heterocyclic compound of claim 11, wherein the heterocyclic compound is represented by Formula 1:

[Formula 1]



wherein in Formula 1,

T_1 is C, Si, or Ge,

ring CY_1 to ring CY_5 are each independently a C_5 - C_{30} carbocyclic group or a C_1 - C_{30} heterocyclic group,

T_{21} is *—C(Z_1)(Z_2)—**, *—Si(Z_1)(Z_2)—**, *—N(Z_1)—**, *—O—**, or *—S—**,

T_{22} is *—C(Z_3)(Z_4)—**, *—Si(Z_3)(Z_4)—**, *—N(Z_3)—**, *—O—**, or *—S—**,

R_1 to R_5 and Z_1 to Z_4 are each independently hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{60} alkyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkenyl group unsubstituted or substituted with at least one R_{10a} , a C_2 - C_{60} alkynyl group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkoxy group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} alkylthio group unsubstituted or substituted with at least one R_{10a} , a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} aryloxy group unsubstituted or substituted with at least one R_{10a} , a C_6 - C_{60} arylthio group unsubstituted or substituted with at least one R_{10a} , —C(Q_1)(Q_2)(Q_3), —Si(Q_1)(Q_2)(Q_3), —N(Q_1)(Q_2), —B(Q_1)(Q_2), —C(=O)(Q_1), —S(=O)₂(Q_1), or —P(=O)(Q_1)(Q_2),

a_1 to a_5 are each independently an integer from 1 to 20,

Ar_1 is a group represented by Formula 1A, a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} , or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,

Z_1 and Z_2 are optionally bonded to each other to form a C_5 - C_{60} carbocyclic group unsubstituted or substituted

with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,
 Z_3 and Z_4 are optionally bonded to each other to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ,
 two or more neighboring groups among R_1 in the number of a1, R_2 in the number of a2, R_3 in the number of a3, R_4 in the number of a4, R_5 in the number of a5, Z_1 to Z_4 , and Ar_1 are optionally bonded to each other to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} , and
 R_{10a} and Q_1 to Q_3 are each the same as defined in Formula 1A.

13. The heterocyclic compound of claim 12, wherein ring CY_1 to ring CY_5 are each independently a benzene group, a naphthalene group, an anthracene group, a phenanthrene group, a triphenylene group, a pyrene group, a chrysene group, a cyclopentadiene group, a furan group, a thiophene group, a silole group, an indene group, a fluorene group, an indole group, a carbazole group, a benzofuran group, a dibenzofuran group, a benzothiophene group, a dibenzothiophene group, a benzosilole group, a dibenzosilole group, an azafluorene group, an azacarbazole group, an azadibenzofuran group, an azadibenzothiophene group, an azadibenzosilole group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a phenanthroline group, a pyrrole group, a pyrazole group, an imidazole group, a triazole group, an oxazole group, an isoxazole group, a thiazole group, an isothiazole group, an oxadiazole group, a thiadiazole group, a benzopyrazole group, a benzimidazole group, a benzoxazole group, a benzothiazole group, a benzoxadiazole group, a benzothiadiazole group, a dibenzooxasiline group, a dibenzothiasiline group, a dibenzodihydroazasiline group, dibenzodihydrodihydrodisiline group, a dibenzodihydrodisiline group, a dibenzodioxine group, a dibenzooxathiine group, a dibenzooxazine group, a dibenzopyran group, a dibenzodithiine group, a dibenzothiazine group, a dibenzothiopyran group, a dibenzocyclohexadiene group, a dibenzodihydropyridine group, or a dibenzodihydropyrazine group.

14. The heterocyclic compound of claim 12, wherein T_{21} is $^*C(Z_1)(Z_2)^{**}$ or $^*Si(Z_1)(Z_2)^{**}$, and T_{22} is $^*C(Z_3)(Z_4)^{**}$ or $^*Si(Z_3)(Z_4)^{**}$.

15. The heterocyclic compound of claim 14, wherein at least one of Conditions 4 and 5 is satisfied:

[Condition 4]

Z_1 and Z_2 are bonded to each other to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} ;

[Condition 5]

Z_3 and Z_4 are bonded to each other to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{10a} .

16. The heterocyclic compound of claim 12, wherein R_1 to R_5 and Z_1 to Z_4 are each independently:

hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, or a C_1 - C_{20} alkoxy group;

a C_1 - C_{20} alkyl group or a C_1 - C_{20} alkoxy group, each substituted with deuterium, $-F$, $-Cl$, $-Br$, $-I$, $-CD_3$, $-CD_2H$, $-CDH_2$, $-CF_3$, $-CF_2H$, $-CFH_2$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{10} alkyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or a combination thereof;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azafluorenyl group, or an azadibenzosilolyl group, each unsubstituted or substituted with deuterium, $-F$, $-Cl$, $-Br$, $-I$, $-CD_3$, $-CD_2H$, $-CDH_2$, $-CF_3$, $-CF_2H$, $-CFH_2$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzothiazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl

group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzo-carbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, $-\text{O}(\text{Q}_{31})$, $-\text{S}(\text{Q}_{31})$, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{P}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, or a combination thereof; or

$-\text{C}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})_2(\text{Q}_1)$, or $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, and

Q_1 to Q_3 and Q_{31} to Q_{33} are each independently: hydrogen; deuterium; $-\text{F}$; $-\text{Cl}$; $-\text{Br}$; $-\text{I}$; a hydroxyl group; a cyano group; a nitro group; a C_1 - C_{60} alkyl group; a C_2 - C_{60} alkenyl group; a C_2 - C_{60} alkynyl group; a C_1 - C_{60} alkoxy group; or a C_5 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group, each unsubstituted or substituted with deuterium, $-\text{F}$, a cyano group, a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a biphenyl group, or a combination thereof.

17. The heterocyclic compound of claim 12, wherein Ar_1 is:

a group represented by Formula 1A; or

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azafluorenyl group, or an azadibenzosilolyl group, each unsubstituted or substituted with deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, $-\text{CD}_3$, $-\text{CD}_2\text{H}$, $-\text{CDH}_2$, $-\text{CF}_3$, $-\text{CF}_2\text{H}$, $-\text{CFH}_2$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a biphenyl group, a


C_1 - C_{10} alkylphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzothiazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, $-\text{O}(\text{Q}_{31})$, $-\text{S}(\text{Q}_{31})$, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{P}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, or a combination thereof, and

Q_{31} to Q_{33} are each independently: hydrogen; deuterium; $-\text{F}$; $-\text{Cl}$; $-\text{Br}$; $-\text{I}$; a hydroxyl group; a cyano group; a nitro group; a C_1 - C_{60} alkyl group; a C_2 - C_{60} alkenyl group; a C_2 - C_{60} alkynyl group; a C_1 - C_{60} alkoxy group; or a C_3 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group, each unsubstituted or substituted with deuterium, $-\text{F}$, a cyano group, a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a biphenyl group, or a combination thereof.

18. The heterocyclic compound of claim 12, wherein Ar_1 is a group represented by Formula 1A.

19. The heterocyclic compound of claim 12, wherein T_{21} and T_{22} are each independently a group represented by Formula 1B:

[Formula 1B]



wherein in Formula 1B,

R_{10a} is the same as defined in Formula 1A,

b_1 and b_2 are each independently an integer from 1 to 4,


T_3 is a single bond, $^*\text{O}^{**}$, $^*\text{S}^{**}$, $^*\text{N}(\text{R}')^{**}$, $^*\text{C}(\text{R}')(\text{R}'')^{**}$, or $^*\text{Si}(\text{R}')(\text{R}'')^{**}$,

R' and R'' are each independently the same as defined in connection with Q_1 in Formula 1A, and

* and ** each independently indicate a binding site to a neighboring atom.

20. The heterocyclic compound of claim 12, wherein the heterocyclic compound is represented by Formula 1-1:

[Formula 1-1]



wherein in Formula 1-1,

T₁, T₂₁, T₂₂, and Ar₁ are each the same as defined in Formula 1,

X₁₁ is C(R₁₁) or N,

X₁₂ is C(R₁₂) or N,

X₁₃ is C(R₁₃) or N,

X₁₄ is C(R₁₄) or N,

X₂₁ is C(R₂₁) or N,

X₂₂ is C(R₂₂) or N,

X₂₃ is C(R₂₃) or N,

X₃₁ is C(R₃₁) or N,

X₃₂ is C(R₃₂) or N,

X₃₃ is C(R₃₃) or N,

X₄₁ is C(R₄₁) or N,

X₄₂ is C(R₄₂) or N,

X₄₃ is C(R₄₃) or N,

X₅₁ is C(R₅₁) or N,

X₅₂ is C(R₅₂) or N,

X₅₃ is C(R₅₃) or N,

X₅₄ is C(R₅₄) or N,

R₁₁ to R₁₄ are each independently the same as defined in connection with R₁ in Formula 1,

R₂₁ to R₂₃ are each independently the same as defined in connection with R₂ in Formula 1,

R₃₁ to R₃₃ are each independently the same as defined in connection with R₃ in Formula 1,

R₄₁ to R₄₃ are each independently the same as defined in connection with R₄ in Formula 1,

R₅₁ to R₅₄ are each independently the same as defined in connection with R₅ in Formula 1, and

two or more neighboring groups among R₁₁ to R₁₄, R₂₁ to R₂₃, R₃₁ to R₃₃, R₄₁ to R₄₃, R₅₁ to R₅₄, Z₁ to Z₄, and Ar₁ are optionally bonded to each other to form a C₃-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{10a} or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{10a}.

* * * * *