

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250280670

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

ISHIYAMA; Yuichiro et al.

DISPLAY PANEL AND DISPLAY DEVICE

Abstract

A display panel includes a flexible substrate. The flexible substrate includes a display region and a peripheral region. A plurality of self-luminescent elements is on a first main face of the display region of the flexible substrate. A plurality of thin film transistor (TFT) circuits is between the first main face and the self-luminescent elements for driving the plurality of self-luminescent elements. A first laminated inorganic film is between the first main face and the self-luminescent elements, with the first laminated inorganic film including a step portion which is a thinned portion and disposed in the peripheral region of the flexible substrate. A second inorganic film covers the self-luminescent elements. A resin layer overlaps the second inorganic film and overlaps at least a portion of the first laminated inorganic film in contact with an end portion of the second inorganic film.

Inventors: ISHIYAMA; Yuichiro (Tokyo, JP), SEKI; Takahiro (Tokyo, JP)

Applicant: JDI Design and Development G.K. (Tokyo, JP)

Family ID: 71521654

Assignee: JDI Design and Development G.K. (Tokyo, JP)

Appl. No.: 19/211941

Filed: May 19, 2025

Foreign Application Priority Data

JP 2019-001931

Jan. 09, 2019

Related U.S. Application Data

parent US continuation 18597502 20240306 parent-grant-document US 12336381 child US 19211941

Publication Classification

Int. Cl.: **H10K59/124** (20230101); **H10K50/844** (20230101); **H10K59/12** (20230101);
H10K59/80 (20230101); **H10K77/10** (20230101)

U.S. Cl.:

CPC **H10K59/124** (20230201); **H10K50/844** (20230201); **H10K59/12** (20230201);
H10K59/873 (20230201); **H10K77/111** (20230201);

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS [0001] This is a Continuation of U.S. patent application Ser. No. 18/597,502, filed Mar. 6, 2024, which is a Continuation of U.S. patent application Ser. No. 17/421,242, filed Jul. 7, 2021 and now U.S. Pat. No. 11,943,958 issued Mar. 26, 2024, which is a National Stage Entry of International Patent Application No. PCT/JP2020/000273, filed Jan. 8, 2020, which claims the benefit of Japanese Patent Application No. 2019-001931, filed Jan. 9, 2019. The disclosure of each of the above-mentioned documents, including the specification, drawings, and claims, is incorporated herein by reference in its entirety.

TECHNICAL FIELD

[0002] The disclosure relates to a display panel and a display apparatus.

BACKGROUND ART

[0003] Display panels including self-luminescent elements such as organic electroluminescent (EL) device use thin film transistors (TFTs) to drive the self-luminescent elements. The display panel includes a frame portion including inorganic films of the TFTs are provided (Reference is made to PTLs 1 to 5 described below, for example).

CITATION LIST

Patent Literature

[0004] [PTL 1] Japanese Unexamined Patent Application Publication No. 2009-37798

[0005] [PTL 2] Japanese Unexamined Patent Application Publication No. 2007-227875

[0006] [PTL 3] Japanese Unexamined Patent Application Publication No. 2014-220489

[0007] [PTL 4] Japanese Unexamined Patent Application Publication No. 2003-195789

[0008] [PTL 5] Japanese Unexamined Patent Application Publication No. 2010-224426

SUMMARY OF INVENTION

[0009] Meanwhile, it is possible to make the display panel described above flexible by using a flexible substrate in the display panel. However, such a flexible display panel is likely to cause cracks in the inorganic film in the frame portion of the display panel while being carried or intentionally bent. Once a crack is formed in the inorganic film, external moisture can enter through the crack to cause a display failure, such as a dark spot. Accordingly, it is desirable to provide a display panel and a display apparatus that make it possible to suppress the occurrence of a display failure, such as a dark spot, due to a crack generated in the inorganic film.

[0010] A first display panel according to one embodiment of the disclosure includes: a flexible substrate; a plurality of self-luminescent elements provided on a first main face of the flexible substrate; and a plurality of TFT circuits provided between the first main face and the plurality of self-luminescent elements and driving the self-luminescent elements. The first display panel has a

first inorganic film, a second inorganic film, and a resin layer. The first inorganic film is provided between the plurality of TFT circuits and the plurality of self-luminescent elements, covers the TFT circuits, and has a step portion. The step portion is a thinned portion of the first inorganic film opposed to an end portion of the flexible substrate. The second inorganic film covers the self-luminescent elements. The resin layer covers the second inorganic film and covers at least a portion of the first inorganic film in contact with an end portion of the second inorganic film.

[0011] A first display apparatus according to one embodiment of the disclosure includes the first display panel and a driver that drives the first display panel.

[0012] In the first display panel and the first display apparatus according to one embodiment of the disclosure, the step portion is formed in the first organic film covering the TFT circuits. The step portion is a thinned portion of the first inorganic film opposed to an end portion of the flexible substrate. Accordingly, if a crack is generated in the end portion of the first inorganic film while the first display panel is being carried or intentionally bent, the step portion helps prevent the crack from expanding. Further, in the first display panel and the first display apparatus according to one embodiment of the disclosure, the second inorganic film covering the self-luminescent elements is covered with the resin layer. Further, at least a portion of the first inorganic film in contact with an end portion of the second inorganic film is also covered with the resin layer. Accordingly, even if a crack generated in the end portion of the first inorganic film expands over the step portion, the resin layer helps prevent the crack from expanding through the portions of the first inorganic film and the second inorganic film covered with the resin layer.

[0013] A second display panel according to one embodiment of the disclosure includes: a flexible substrate; a plurality of self-luminescent elements provided on a first main face of the flexible substrate; and a plurality of TFT circuits provided between the first main face and the plurality of self-luminescent elements and driving the self-luminescent elements. The second display panel further includes an inorganic film and a resin layer. The inorganic layer is provided between the flexible substrate and the plurality of TFT circuits, covers the first main face, and has a step portion. The step portion is a thinned portion of the inorganic film opposed to an end portion of the flexible substrate. The resin layer covers the other portion of the inorganic film other than the thinned portion.

[0014] A second display apparatus according to one embodiment of the disclosure includes the second display panel and a driver that drives the second display panel.

[0015] In the second display panel and the second display apparatus according to one embodiment of the disclosure, the step portion is formed in the inorganic film covering the first main face of the flexible substrate. The step portion is a thinned portion of the inorganic film opposed to an end portion of the flexible substrate. Accordingly, if a crack is generated in the end portion of the inorganic film while the second display panel is being carried or intentionally bent, for example, the step portion helps prevent the crack from expanding. Further, in the second display panel and the second display apparatus according to one embodiment of the disclosure, the other portion of the inorganic film other than the thinned portion is covered with the resin layer. Accordingly, even if the crack generated in the end portion of the inorganic film expands over the step portion, the resin layer helps prevent the crack from expanding through the portion of the inorganic film covered with the resin layer.

[0016] In the first display panel and the first display apparatus according to one embodiment of the disclosure, the resin layer helps prevent a crack from expanding. Accordingly, it is possible to suppress the occurrence of a display failure, such as a dark spot, due to the crack generated in the first inorganic film.

[0017] In the second display panel and the second display apparatus according to one embodiment of the disclosure, the resin layer helps prevent a crack from expanding. Accordingly, it is possible to suppress the occurrence of a display failure, such as a dark spot, due to the crack generated in the inorganic film.

[0018] It is to be noted that the effects described hereinabove are mere examples. The effects according to an embodiment of the disclosure are not limited to those described hereinabove. The disclosure may further include other effects in addition to the effects described hereinabove.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0019] FIG. 1 is a diagram illustrating a schematic configuration example of a display apparatus according to a first embodiment of the disclosure.

[0020] FIG. 2 is a diagram illustrating an exemplary connection between a display panel, a controller, and a driver illustrated in FIG. 1.

[0021] FIG. 3 is a diagram illustrating an exemplary circuit configuration of each pixel in the display apparatus illustrated in FIG. 1.

[0022] FIG. 4 is a diagram illustrating an exemplary cross-sectional configuration taken along a line A-A in FIG. 2.

[0023] FIG. 5 is a diagram illustrating an exemplary cross-sectional configuration taken along a line B-B in FIG. 2.

[0024] FIG. 6 is an enlarged view of a step portion illustrated in FIG. 4.

[0025] FIG. 7A and FIG. 7B are diagrams illustrating a design model of the step portion illustrated in FIG. 6.

[0026] FIG. 8A is a diagram illustrating an exemplary step of manufacturing the display panel illustrated in FIG. 2.

[0027] FIG. 8B is a diagram illustrating an exemplary manufacturing step following the step illustrated in FIG. 8A.

[0028] FIG. 8C (a) and FIG. 8C (b) are diagrams illustrating an exemplary manufacturing step following the step illustrated in FIG. 8B.

[0029] FIG. 8D (a) and FIG. 8D (b) are diagrams illustrating an exemplary manufacturing step following the step illustrated in FIG. 8C (a) and FIG. 8C (b).

[0030] FIG. 8E (a) and FIG. 8E (b) are diagrams illustrating an exemplary manufacturing step following the step illustrated in FIG. 8D (a) and FIG. 8D (b).

[0031] FIG. 8F (a) and FIG. 8F (b) are diagrams illustrating an exemplary manufacturing step following the step illustrated in FIG. 8E (a) and FIG. 8E (b).

[0032] FIG. 9A is a diagram illustrating an exemplary step of manufacturing the display panel illustrated in FIG. 2.

[0033] FIG. 9B is a diagram illustrating an exemplary manufacturing step following the step illustrated in FIG. 9A.

[0034] FIG. 9C is a diagram illustrating an exemplary manufacturing step following the step illustrated in FIG. 9B.

[0035] FIG. 9D is a diagram illustrating an exemplary manufacturing step following the step illustrated in FIG. 9C.

[0036] FIG. 9E is a diagram illustrating an exemplary manufacturing step following the step illustrated in FIG. 9D.

[0037] FIG. 9F is a diagram illustrating an exemplary manufacturing step following the step illustrated in FIG. 9E.

[0038] FIG. 9G (a) and FIG. 9G (b) are diagrams illustrating an exemplary manufacturing step following the step illustrated in FIG. 9F.

[0039] FIG. 9H (a) and FIG. 9H (b) are diagrams illustrating an exemplary manufacturing step following the step illustrated in FIG. 9G (a) and FIG. 9G (b).

[0040] FIG. 10A (a) and FIG. 10A (b) are diagrams illustrating an exemplary step of manufacturing

the display panel illustrated in FIG. 2.

[0041] FIG. 10B (a) and FIG. 10B (b) are diagrams illustrating an exemplary manufacturing step following the step illustrated in FIG. 10A (a) and FIG. 10A (b).

[0042] FIG. 10C (a) and FIG. 10C (b) are diagrams illustrating an exemplary manufacturing step following the step illustrated in FIG. 10B (a) and FIG. 10B (b).

[0043] FIG. 11 is a diagram illustrating a cross-sectional configuration taken along the line A-A in FIG. 2 according to one modification example.

[0044] FIG. 12 is a diagram illustrating a cross-sectional configuration taken along the line A-A in FIG. 2 according to one modification example.

[0045] FIG. 13 is a diagram illustrating a cross-sectional configuration taken along the line A-A in FIG. 2 according to one modification example.

[0046] FIG. 14 is a diagram illustrating a cross-sectional configuration taken along the line A-A in FIG. 2 according to one modification example.

[0047] FIG. 15 is a diagram illustrating a cross-sectional configuration taken along the line A-A in FIG. 2 according to one modification example.

[0048] FIG. 16 is a diagram illustrating one modification example of the step portion illustrated in FIGS. 4 and 11 to 15.

[0049] FIG. 17 is a diagram illustrating one modification example of the cross-sectional configuration illustrated in FIG. 4.

[0050] FIG. 18 is a diagram illustrating one modification example of the cross-sectional configuration illustrated in FIG. 12.

[0051] FIG. 19 is a diagram illustrating one modification example of the cross-sectional configuration illustrated in FIG. 14.

MODES FOR CARRYING OUT THE INVENTION

[0052] In the following, some embodiments of the disclosure are described in detail with reference to the accompanying drawings. Note that the embodiments described below are preferred specific examples of the disclosure. Thus, factors including, without limitation, numerical values, shapes, materials, components, positions of the components, and how the components are coupled to each other are illustrative only and not to be construed as limiting to the disclosure. Further, elements in the following embodiments which are not recited in a most-generic independent claim of the disclosure are optional and may be provided on an as-needed basis. The drawings are schematic and are not intended to be drawn to scale and not necessarily strictly illustrated. Note that the like elements are denoted with the same reference numerals, and any redundant description thereof is omitted or simplified. Note that the description is given in the following order: [0053] 1.

Embodiments (Display Apparatus) [0054] 2. Modification Examples (Display Apparatus)

1. Embodiments

[Configuration]

[0055] FIG. 1 illustrates a schematic configuration example of a display apparatus 1 according to one embodiment of the disclosure. The display apparatus 1 includes a display panel 10, a controller 20, and a driver 30, for example. FIG. 2 illustrates an exemplary connection between the display panel 10, the controller 20, and the driver 30. FIG. 3 illustrates an exemplary circuit configuration of each pixel 11 provided in the display apparatus 1.

[0056] The display panel 10 includes a plurality of pixels 11 arranged in matrix. The plurality of pixels 11 are provided in a display region 10A of the display panel 10. The display region 10A corresponds to an image display surface of the display panel 10. The display panel 10 has a frame region 10B surrounding the display region 10A. The frame region 10B has a frame shape surrounding the display region 10A. A plurality of mounting terminals are provided at one side of the frame region 10B. The plurality of mounting terminals 53 are electrically connected to the plurality of pixels 11 and flexible printed circuits (FPCs) 52. The controller 20 and the driver 30 are mounted on a control base 51 and electrically connected to the display panel 10 (the plurality of

pixels **11**) via the FPCs **52**. The controller **20** and the driver **30** drive the display panel **10** (the plurality of pixels **11**) on the basis of an image signal Din received from an external device.

[Display Panel **10**]

[0057] In response to active-matrix driving of the pixels **11** performed by the controller **20** and the driver **30**, the display panel **10** displays an image on the display region **10A** on the basis of the image signal Din received from the external device. The display panel **10** includes multiple scanning lines WSL extending in a row direction, multiple signal lines DTL and multiple power lines DSL extending in a column direction, and the plurality of pixels **11** arranged in matrix.

[0058] The scanning line WSL is used to select the pixels **11**. For example, the scanning line WSL supplies a selection pulse to any of the pixels **11** to select the pixels **11** on a predetermined unit basis (e.g., a pixel-row basis). The signal line DTL is used to supply a signal voltage corresponding to the image signal Din to each pixel **11**. For example, the signal line DTL supplies a data pulse including a signal voltage to each pixel **11**. The power line DSL supplies electric power to each pixel **11**.

[0059] The pixels **11** in the display panel **10** include ones emitting red light, ones emitting green light, and ones emitting blue light. The pixel **11** emitting red light, the pixel **11** emitting green light, and the pixel **11** emitting blue light constitute a display pixel, which is a unit of display of a color image. Each display pixel may further include a pixel **11** emitting light of another color (e.g., white or yellow). Alternatively, each display pixel may include a plurality of pixels **11** emitting light of the same color (e.g., two pixels **11** emitting blue light).

[0060] Each of the signal lines DTL is coupled to an output terminal of a horizontal selector **31** to be described later. Each of the signal lines DTL is allocated to its corresponding pixel column, for example. Each of the scanning lines WSL is coupled to an output terminal of a write scanner **32** to be described later. Each of the scanning lines WSL is allocated to its corresponding pixel row, for example. Each of the power lines DSL is coupled to an output terminal of a power source. Each of the power lines DSL is allocated to its corresponding pixel row, for example.

[0061] Each pixel **11** includes a pixel circuit **11-1** and an organic electroluminescent element **11-2**. The configuration of the organic electroluminescent element **11-2** will be described later.

[0062] The pixel circuit **11-1** controls light emission and light extinction of the organic electroluminescent element **11-2**. The pixel circuit **11-1** has a function of holding a voltage written in each pixel **11** through write scanning. The pixel circuit **11-1** includes a driving transistor Tr1, a write transistor Tr2, and a storage capacitor Cs, for example.

[0063] The write transistor Tr2 controls an application of the signal voltage corresponding to the image signal Din to a gate of the driving transistor Tr1. For example, the write transistor Tr2 samples the voltage of the signal line DTL and write the sampled voltage into the gate of the driving transistor Tr1. The driving transistor Tr1 is coupled in series to the organic electroluminescent element **11-2**. The driving transistor Tr1 drives the organic electroluminescent element **11-2**. The driving transistor Tr1 controls an electric current flowing in the organic electroluminescent element **11-2** on the basis of the magnitude of the voltage sampled at the write transistor Tr2. The storage capacitor Cs holds a predetermined voltage between the gate and the source of the driving transistor Tr1. The storage capacitor Cs holds a constant voltage between the gate and the source of the driving transistor Tr1 for a predetermined period of time. Note that the pixel circuit **11-1** may have the 2Tr1C circuit configuration described above and additional capacitors and transistors. Alternatively, the pixel circuit **11-1** may have a circuit configuration different from the 2Tr1C circuit configuration described above.

[0064] Each of the signal lines DTL is coupled to the output terminal of the horizontal selector **31** to be described later and the source or drain of the write transistor Tr2. Each of the scanning lines WSL is coupled to the output terminal of the write scanner **32** to be described later and the gate of the write transistor Tr2. Each of the power lines DSL is coupled to a power supply circuit and the source or drain of the driving transistor Tr1.

[0065] The gate of the write transistor Tr2 is coupled to the scanning line WSL. One of the source and drain of the write transistor Tr2 is coupled to the signal line DTL. The other of the source and drain of the write transistor Tr2, which is not coupled to the signal line DTL, is coupled to the gate of the driving transistor Tr1. One of the source and drain of the driving transistor Tr1 is coupled to the power line DSL. The other of the source and drain of the driving transistor Tr1, which is not coupled to the power line DSL, is coupled to an anode **21** of the organic electroluminescent element **11-2**. One end of the storage capacitor Cs is coupled to the gate of the driving transistor Tr1. The other end of the storage capacitor Cs is coupled to the source or drain of the driving transistor Tr1 whichever is adjacent to the organic electroluminescent element **11-2**.

[0066] The driving transistor Tr1 and the write transistor Tr2 are general thin-film transistors (TFTs) and may have a reverse staggered structure (a so-called bottom gate type) or a staggered structure (top gate type). The structure of the driving transistor Tr1 and the write transistor Tr2 should not be limited to a particular structure.

[Driver **30**]

[0067] The driver **30** includes the horizontal selector **31** and the write scanner **32**, for example. The horizontal selector **31** applies an analog signal voltage received from the controller **20** to each of the signal lines DTL in response to (in synchronization with) a control signal, for example. The write scanner **32** scans the pixels **11** on a predetermined unit basis.

[Controller **20**]

[0068] The controller **20** will now be described. The controller **20** performs a predetermined correction on the digital image signal Din received from an external device, for example, and generates a signal voltage based on the image signal generated as a result of the correction. The controller **20** outputs the generated signal voltage to the horizontal selector **31**, for example. For example, the controller **20** outputs a control signal to each circuit in the driver **30** in response to (in synchronization with) the control signal obtained from the image signal Din.

[0069] Next, with reference to FIGS. **4** and **5**, a cross-sectional configuration of the display panel **10** is described. FIG. **4** illustrates an exemplary cross-sectional configuration taken along a line A-A in FIG. **3**. FIG. **5** illustrates an exemplary cross-sectional configuration taken along a line B-B in FIG. **3**.

[0070] The display panel **10** includes a flexible substrate **41** and a plurality of organic electroluminescent elements **44A** provided on a surface **41A** (first main face) of the flexible substrate **41**. The flexible substrate **41** is a film or sheet made of resin, for example. The flexible substrate **41** includes a methacrylic resin, such as polyimide (PI) or polymethylmethacrylate (PMMA), a polyester, such as polyethylene terephthalate (PET), polyethylene naphthalate (PEN), or polybutylene naphthalate (PBN), or a polycarbonate resin. The organic electroluminescent elements **44A** correspond to the organic electroluminescent elements **11-2** described above.

[0071] The display panel **10** includes TFT circuits **43A** provided between the surface **41A** of the flexible substrate **41** and the organic electroluminescent elements **44A**. The TFT circuits **43A** drive the organic electroluminescent elements **44A**. The TFT circuits **43A** corresponds to the pixel circuits **11-1** described above.

[0072] The display panel **10** includes an inorganic insulating film **43B** (first inorganic film) provided between the TFT circuits **43A** and the organic electroluminescent elements **44A**. The inorganic insulating film **43B** covers the TFT circuits **43A**. The inorganic insulating film **43B** includes an inorganic material having low moisture absorbency, such as silicon oxide (SiOx), silicon nitride (SiNx), silicon nitride oxide (SiNxOy), titanium oxide (TiOx), or aluminum oxide (AlxOy).

[0073] The inorganic insulating film **43B** has a step portion **43C**. The step portion **43C** is a thinned portion of the inorganic insulating film **43B** opposed to an end portion of the flexible substrate **41**. The portion of the inorganic insulating film **43B** opposed to the end portion of the flexible substrate **41** is thinner than the other portion of the inorganic insulating film **43B** opposed to the organic

electroluminescent elements **44A**. The difference in thickness between the portion opposed to the end portion of the flexible substrate **41** and the portion opposed to the organic electroluminescent elements **44A** forms the step portion **43C**. The step portion **43C** is formed in the frame region **10B**. The step portion **43C** is formed so as not to be opposed to at least the mounting terminals **53**. For example, the step portion **43C** is formed along three sides of the frame region **10B** other than the side along which the mounting terminals **53** are formed. The mounting terminals **53** are formed in a flat region of the surface of the inorganic insulating film **43B** in which the step portion **43C** is not formed, and are exposed on the surface of the inorganic insulating film **43B**. Alternatively, the step portion **43C** is formed on two sides of the frame region **10B** perpendicular to the side along which the mounting terminals **53** are formed. In such a case, the display panel **10** is foldable only in the direction perpendicular to the side of the frame region **10B** along which the mounting terminals **53** are formed.

[0074] The display panel **10** includes an inorganic insulating film **45** (second inorganic film) covering the organic electroluminescent elements **44A**, and a resin layer **46** covering the inorganic insulating film **45** and covering at least a portion of the inorganic insulating film **43B** in contact with an end portion of the inorganic insulating film **45**. For example, the inorganic insulating film **45** includes an inorganic material having low moisture absorbency, such as silicon oxide (SiOx), silicon nitride (SiNx), silicon nitride oxide (SiNxOy), titanium oxide (TiOx), or aluminum oxide (AlxOy). An end portion of the resin layer **46** may be formed on the step portion **43C**. In such a case, the resin layer **46** is in contact with the entire surface of the inorganic insulating film **45** and also in contact with from a portion of the inorganic insulating film **43B** in contact with the end portion of the inorganic insulating film **45** to the step portion **43C**. The resin layer **46** also serves as an adhesive layer, and includes an epoxy resin or an acrylic resin, for example. The resin layer **46** may include a thermosetting resin or an ultraviolet curing resin, for example.

[0075] In the display panel **10**, the organic electroluminescent elements **44A** are separated from each other by opening definition insulating portions **44B**. Each of the organic electroluminescent elements **44A** defined in outline is provided in each pixel **11**. The opening definition insulating portions **44B** and the organic electroluminescent elements **44A** are formed on the same plane, forming an EL element layer **44**.

[0076] The display panel **10** includes a UC barrier layer **42** between the flexible substrate **41** and the TFT circuits **43A**. The UC barrier layer **42** entirely covers the surface **41A** of the flexible substrate **41**. The UC barrier layer **42** is an inorganic insulating film including an inorganic material having low moisture absorbency, such as silicon oxide (SiOx), silicon nitride (SiNx), silicon nitride oxide (SiNxOy), titanium oxide (TiOx), or aluminum oxide (AlxOy). The UC barrier layer **42** may be a single layer or a laminated layer including layers made of different materials.

[0077] The display panel **10** includes a sealing layer **47** provided so as to be opposed to the flexible substrate **41** and being in contact with the resin layer **46**. The sealing layer **47** includes a resin material, such as an epoxy resin or a vinyl resin. The sealing layer **47** may have an optical function. The sealing layer **47** may be a polarization plate, for example.

[0078] The display panel **10** includes, in order, a resin layer **48** and a reinforcement layer **49** on a rear surface **41B** of the flexible substrate **41**. The resin layer **48** entirely covers the rear surface **41B** of the flexible substrate **41**. For example, the resin layer **48** serves as an adhesive layer that adheres the flexible substrate **41** to the reinforcement layer **49**. The resin layer **48** includes an epoxy resin or an acrylic resin, for example. The reinforcement layer **49** serves as a reinforcing member that maintains the strength of the display panel **10**, and a protective member that protects the back face of the display panel **10**. For example, the reinforcement layer **49** includes a resin material, such as PET or PI, or a metal material, such as Al, Cu, or SUS.

[0079] FIG. **6** illustrates the step portion **43C** in an enlarged manner. The portion of the inorganic insulating film **43B** opposed to the end portion of the flexible substrate **41** has a thickness *tb*. The portion of the inorganic insulating film **43B** opposed to the organic electroluminescent elements

44A has a thickness t_a . The length between the portion of the inorganic insulating film **43B** in contact with the end portion of the inorganic insulating film **45** and the end portion of the inorganic insulating film **43B** is indicated by W_a , and the length between the step portion **43C** and the end portion of the inorganic insulating film **43B** is indicated by W_b . In this case, it is preferable that the thickness t_b be 3% or greater and 50% or less of the thickness t_a . The length W_a is within a practical range of a narrow frame panel, for example, 1 mm or greater and 10 mm or less. The lower limit of the length W_b is a minimum length that prevents an initially-generated crack from reaching the step portion **43C**, and may be, for example, 0.1 mm. The upper limit of the length W_b is a half of a maximum possible length of the length W_a , and may be, for example, 5 mm.

[0080] FIG. 7 illustrates a design model of the step portion **43C**. As illustrated in FIG. 7(A), when a plate object is stretched from both sides with a force F , a stress $\sigma_{sub.0}$ exerted on a cross-section perpendicular to the stretching direction is represented by $F/(Bt)$, where “ B ” denotes the width of the object, and “ t ” denotes the thickness of the object. Further, as illustrated in FIG. 7(B), when an object in which an initial crack in the form of an oval hole is formed, is stretched from both sides with the force F , a stress $\sigma_{sub.max}$ exerted on an end portion of the oval hole is represented by $\sigma_{sub.0} \times (1 + 2(a/\rho)^{sup.1/2})$, where “ $2a$ ” denotes the longitudinal length of the oval hole, “ $2b$ ” denotes the lateral length of the oval hole, and “ $\rho (=b^{sup.2}/a)$ ” denotes the radius of curvature of an end portion of the oval hole.

[0081] Here, the stress $\sigma_{sub.max}$ is in proportion to “ $1/t$ ”. Thus, a relationship represented by $\sigma_{sub.max1}/\sigma_{sub.max2} = t_2/t_1$ is hold between the stress $\sigma_{sub.max1}$ exerted on the end portion of the oval hole formed in the inorganic insulating film **43B** at a position opposed to the end portion of the flexible substrate **41** and the stress $\sigma_{sub.max2}$ exerted on the end portion of the oval hole formed at a position opposed to the organic electroluminescent elements **44A**.

[0082] Accordingly, assuming that a crack is generated in a film by a stress greater than a predetermined level, it is possible to make the portion of the inorganic insulating film **43B** opposed to the organic electroluminescent elements **44A** twice as resistant to a crack as the portion of the inorganic insulating film **43B** opposed to the end of the flexible substrate **41** by setting the thickness t_a to be twice of the thickness t_b , for example.

[Manufacturing Method]

[0083] An exemplary method of manufacturing the display panel **10** will now be described. FIGS. **8A** to **8F** are cross-sectional views of the display panel **10** illustrating exemplary steps for manufacturing the display panel **10**.

[0084] First, the flexible substrate **41**, the UC barrier layer **42**, and the TFT layer **43** are formed on a large supporting glass **100** (FIG. **8A**). Thereafter, the EL element layer **44** and the inorganic insulating film **45** are formed in each section corresponding to the size of the display panel **10** (FIG. **8A**). Thereafter, the sealing layer **47** is attached to the inorganic insulating film **45** with the resin layer **46** provided therebetween in each section corresponding to the size of the display panel **10** (FIG. **8B**). Thereafter, the large supporting glass **100** is separated into the sections each corresponding to the size of the display panel **10** (FIGS. **8C(a)** and **8C(b)**). FIG. **8C(a)** illustrates an exemplary cross-sectional configuration taken along the line A-A in FIG. **2**, and FIG. **8C(b)** illustrates an exemplary cross-sectional configuration taken along the line B-B in FIG. **2**.

[0085] Next, the inorganic insulating film **43B** of the TFT layer **43** is selectively etched using the sealing layer **47** as a mask (FIGS. **8D(a)** and **8D(b)**). The step portion **43C** is thereby formed in the inorganic insulating film **43B**. While the step portion **43C** is being formed (i.e., while the inorganic insulating film **43B** is being selectively etched using the sealing layer **47** as a mask), the inorganic insulating film **43B** is etched into a desired thickness t_b for a predetermined etching time that is calculated based on a preliminarily calculated etching rate of the inorganic insulating film **43B**, for example. The front surfaces of the mounting terminals **53** are thereby exposed. Thereafter, the FPCs **52** are mounted on the respective mounting terminals **53** (FIGS. **8E(a)** and **8E(b)**). Lastly, the supporting glass **100** is removed, and the reinforcement layer **49** is attached to the rear surface of

the flexible substrate **41** with the resin layer **48** provided therebetween (FIGS. **8F(a)** and **8F(b)**). The display panel **10** according to the present embodiment is manufactured as described above. [0086] The display panel **10** may be produced by a method other than the method described above. FIGS. **9A** to **9H** are cross-sectional views illustrating exemplary steps for manufacturing the display panel **10**.

[0087] First, the flexible substrate **41**, the UC barrier layer **42**, and the TFT layer **43** are formed on the large supporting glass **100** (FIG. **9A**). Thereafter, the EL element layer **44** and the inorganic insulating film **45** are formed in each section corresponding to the size of the display panel **10** (FIG. **9A**). Thereafter, a supporting film **120** is attached to the entire surface including the inorganic insulating film **45** with the resin layer **130** provided therebetween, and then the supporting glass **100** is removed (FIG. **9B**). Thereafter, the reinforcement layer **49** is attached to the rear surface of the flexible substrate **41** with the resin layer **48** provided therebetween (FIG. **9C**).

[0088] Next, the supporting film **120** and the resin layer **130** are removed (FIG. **9D**), and the sealing layer **47** is attached to the inorganic insulating film **45** with the resin layer **46** provided therebetween in each section corresponding to the size of the display panel **10** (FIG. **9E**).

Thereafter, the inorganic insulating film **43B** of the TFT layer **43** is selectively etched using the sealing layer **47** as a mask (FIG. **9F**). The step portion **43C** is thereby formed in the inorganic insulating film **43B**. The front surfaces of the mounting terminals **53** are thereby exposed.

Thereafter, the flexible substrate **41** is separated into the sections each corresponding to the size of the display panel **10** (FIGS. **9G(a)** and **9G(b)**). FIG. **9G(a)** illustrates an exemplary cross-sectional configuration taken along the line A-A in FIG. **2**, and FIG. **9G(b)** illustrates an exemplary cross-sectional configuration taken along the line B-B in FIG. **2**. Lastly, the FPCs **52** are mounted on the respective mounting terminals **53** (FIGS. **9H(a)** and **9H(b)**). The display panel **10** of the present embodiment is manufactured as described above.

[0089] The display panel **10** may be produced by a method other than the methods described above. FIGS. **10A** to **10C** are cross-sectional views illustrating exemplary steps for manufacturing the display panel **10**.

[0090] First, the same processes as those illustrated in FIGS. **9A** to **9C** are performed. Thereafter, the flexible substrate **41** is separated into sections each corresponding to the size of the display panel **10** (FIGS. **10A(a)** and **10A(b)**). FIG. **10A(a)** illustrates an exemplary cross-sectional configuration taken along the line A-A in FIG. **2**, and FIG. **10A(b)** illustrates an exemplary cross-sectional configuration taken along the line B-B in FIG. **2**. Thereafter, the supporting film **120** and the resin layer **130** are removed (FIGS. **10B(a)** and **10B(b)**), and the sealing layer **47** is attached to the inorganic insulating film **45** with the resin layer **46** provided therebetween in each section corresponding to the size of the display panel **10** (FIGS. **10C(a)** and **10C(b)**).

[0091] Next, the inorganic insulating film **43B** of the TFT layer **43** is selectively etched using the sealing layer **47** as a mask (FIGS. **9G(a)** and **9G(b)**). The step portion **43C** is thereby formed in the inorganic insulating film **43B**. The front surfaces of the mounting terminals **53** are thereby exposed. Lastly, the FPCs **52** are mounted on the respective mounting terminals **53** (FIGS. **9H(a)** and **9H(b)**). The display panel **10** according to the present embodiment is manufactured as described above.

[Effects]

[0092] Some effects of the display panel **10** and the display apparatus **1** according to the present embodiment will now be described.

[0093] In the display panel including the self-luminescent element such as an organic electroluminescent element, the self-luminescent element is driven by the TFT. In the frame region of the display panel, the inorganic film of the TFT is provided. Meanwhile, it is possible to make the display panel flexible by using a flexible substrate in the display panel. However, such a flexible display panel is likely to cause a crack in the inorganic film in the frame portion of the display panel while being carried or intentionally bent. Once a crack is formed in the inorganic film, external moisture can enter through the crack to cause display failures, such as a dark spot.

[0094] However, in the present embodiment, the inorganic insulating film **43B** covering the TFT circuit **43A** has the step portion **43C**, which is the thinned portion of the inorganic insulating film **43B** opposed to the end portion of the flexible substrate **41**. If a crack is generated at the end portion of the inorganic insulating film **43B** while the display panel **10** is being carried or intentionally bent, the step portion **43C** helps prevent the crack from expanding. Further, in the present embodiment, the inorganic insulating film **45** covering each organic electroluminescent element **44A** is covered with the resin layer **46**. The resin layer **46** also covers at least a portion of the inorganic insulating film **43B** in contact with the end portion of the inorganic insulating film **45**. Accordingly, even if a crack generated in the end portion of the inorganic insulating film **43B** expands over the step portion **43C**, the resin layer **46** helps prevent the crack from expanding through the portions of the inorganic insulating film **43B** and the inorganic insulating film **45** covered with the resin layer **46**. As a result, it is possible to suppress the occurrence of a display failure, such as a dark spot, due to the crack generated in the inorganic insulating film **43B**.

[0095] Further, in the present embodiment, the end portion of the resin layer **46** is formed on the step portion **43C**. In this case, the resin layer **46** is in contact with the entire surface of the inorganic insulating film **45** and also in contact with from the portion of the inorganic insulating film **43B** in contact with the end portion of the inorganic insulating film **45** to the step portion **43C**.

Accordingly, even if a crack generated in the end portion of the inorganic insulating film **43B** expands over the step portion **43C**, the resin layer **46** helps prevent the crack from expanding through the portions of the inorganic insulating film **43B** and the inorganic insulating film **45** covered with the resin layer **46**. As a result, it is possible to suppress the occurrence of a display failure, such as a dark spot, due to the crack generated in the inorganic insulating film **43B**.

[0096] Further, in the present embodiment, the step portion **43C** is formed so as not to be opposed to at least the mounting terminals **53**. That is, the step portion **43C** does not reach the region of the display panel **10** not to be intentionally bent. Thus, it is possible to provide the mounting terminals **53** in flat portions. As a result, the FPCs **52** are easily coupled to the mounting terminals **53**.

2. Modification Examples

[0097] Modification examples of the display panel **10** according to the foregoing embodiment will now be described.

Modification Example A

[0098] FIG. **11** illustrates a cross-sectional configuration taken along the line A-A in FIG. **4** according to one modification example. In the foregoing embodiment, the step portion **43C** of the inorganic insulating film **43B** and the vicinity thereof may be exposed without being covered with the resin layer **46**. Even in such a case, the resin layer **46** covers at least the portion of inorganic insulating film **43B** in contact with the end portion of the inorganic insulating film **45**. The end portion of the resin layer **46** is in contact with the surface of the inorganic insulating film **43B** in a region between the end portion of the inorganic insulating film **45** and the step portion **43C**. A step portion **43D** is formed in the portion where the end portion of the resin layer **46** is in contact with the surface of the inorganic insulating film **43B**.

[0099] Accordingly, even if a crack generated in the end portion of the inorganic insulating film **43B** expands over the step portion **43C**, the resin layer **46** and the step portion **43D** help prevent the crack from expanding through the portions of the inorganic insulating films **43B** and **45** covered with the resin layer. As a result, it is possible to suppress the occurrence of a display failure, such as a dark spot, due to the crack generated in the inorganic insulating film **43B**.

Modification Example B

[0100] FIGS. **12** and **13** illustrate a cross-sectional configuration taken along the line A-A in FIG. **4** according to one modification example. In the foregoing embodiment and Modification Example A, the display panel **10** may include a resin layer **54** and a UC barrier layer **57** between the UC barrier layer **42** and the TFT layer **43**. The resin layer **54** includes an epoxy resin or an acrylic resin, for example. The UC barrier layer **57** is an inorganic insulating film including an inorganic material

having low moisture absorptency, such as silicon oxide (SiOx), silicon nitride (SiNx), silicon nitride oxide (SiNxOy), titanium oxide (TiOx), or aluminum oxide (AlxOy). The UC barrier layer **57** may be a single layer or a laminated layer including layers made of different materials. Accordingly, if a crack is generated at the UC barrier layers **42** or **57** while the display panel **10** is being carried or intentionally bent, for example, the resin layer **54** provided between the inorganic insulating film **43B** or **45** and the UC barrier layer **42** helps prevent the crack from expanding through the inorganic insulating film **43B** or **45**. As a result, it is possible to suppress the occurrence of a display failure, such as a dark spot, due to the crack generated in the inorganic insulating film **43B**.
Modification Example C

[0101] FIG. **14** illustrates a cross-sectional configuration taken along the line A-A in FIG. **4** according to one modification example. FIG. **14** illustrates an modification example of the cross-sectional configuration illustrated in FIG. **12**. In Modification Example B described above, the step portion **43C** is formed in the inorganic insulating film **43B**. However, in Modification Example B described above, the inorganic insulating film **43B** does not include the step portion **43C**, and the UC barrier layer **42** may include the step portion **42A** instead, as illustrated in FIG. **14**, for example.

[0102] In this modification example, the surface of the end portion of the inorganic insulating film **43B** does not include step portion **43C** and is substantially flat. In contrast, the UC barrier layer **42** has the step portion **42A**, which is a thinned portion of the UC barrier layer **42** opposed to the end portion of the flexible substrate **41**. The portion of the UC barrier layer **42** opposed to the end portion of the flexible substrate **41** is thinner than the other portion of the UC barrier layer **42** opposed to the organic electroluminescent elements **44A**. The difference in thickness between the portion opposed to the end portion of the flexible substrate **41** and the portion opposed to the organic electroluminescent elements **44A** forms the step portion **42A**. The step portion **42A** is formed in the frame region **10B**. The step portion **42A** is formed so as not to be opposed to at least the mounting terminals **53**. For example, the step portion **42A** is formed along three sides of the frame region **10B** other than the side along which the mounting terminals **53** are formed. The mounting terminals **53** are formed in a region of the surface of the UC barrier layer **42** opposed to the flat region in which step portion **42A** is not formed. Alternatively, the step portion **42A** is formed on two sides of the frame region **10B** perpendicular to the side along which the mounting terminals **53** are formed. In such a case, the display panel **10** is foldable only in the direction perpendicular to the side of the frame region **10B** along which the mounting terminals **53** are formed.

[0103] In this modification example, the resin layer **54** covers the portion of the UC barrier layer **42** other than the thinned portion of the UC barrier layer **42**. The end portion of the resin layer **54** may be formed on the step portion **42A**. In this case, the resin layer **54** is in contact with from a portion of the UC barrier layer **42** opposed to the TFT circuits **43A** to the step portion **42A**. The resin layer **54** may include polyimide, an epoxy resin, or an acrylic resin, for example.

[0104] Accordingly, even if a crack generated in the end portion of the UC barrier layer **42** expands over the step portion **42A**, the resin layer **54** helps prevent the crack from expanding through the portion of the UC barrier layer **42** covered with the resin layer **54**. As a result, it is possible to suppress the occurrence of a display failure, such as a dark spot, due to the crack generated in the UC barrier layer **42**.

[0105] Further, in this modification example, the end portion of the TFT layer **43** provided in the vicinity of the step portion **42A** may be exposed without being covered with the resin layer **46**, as illustrated in FIG. **15**, for example. Even in such a case, the resin layer **46** covers at least the portion of the inorganic insulating film **43B** in contact with the end portion of the inorganic insulating film **45**. Here, the end portion of the resin layer **46** is in contact with the surface of the inorganic insulating film **43B** in the region between the end portion of the inorganic insulating film **45** and the end portion of the inorganic insulating film **43B**. The step portion **43D** is formed at a

portion where the end portion of the resin layer **46** is in contact with the surface of the inorganic insulating film **43B**.

[0106] Accordingly, even if a crack is generated in the end portion of the inorganic insulating film **43B**, the resin layer **46** and the step portion **43D** help prevent the crack from expanding through the portions of the inorganic insulating films **43B** and **45** covered with the resin layer **46**. As a result, it is possible to suppress the occurrence of a display failure, such as a dark spot, due to the crack generated in the inorganic insulating film **43B**.

[0107] Although the disclosure is described hereinabove with reference to the embodiments and modification examples, the disclosure is not limited thereto and may be modified in various ways. It should be appreciated that the effects described herein are mere examples, and the effects of the disclosure should not be limited to the effects described herein. The disclosure may provide effects other than those described herein.

Modification Example D

[0108] FIG. **16** illustrates the step portion **42A** in the UC barrier layer **42** or the step portion **43C** in the inorganic insulating film **43B** in an enlarged manner. In the foregoing embodiments and Modification Examples A, B, and C, the UC barrier layer **42** and the inorganic insulating film **43B** may have a configuration in which an insulating material constituting the bottom surfaces of the step portions **42A** and **43C** and an insulating material constituting the side surfaces of the step portions **42A** and **43C** are different from each other. In the foregoing embodiments and Modification Examples A, B, and C, the UC barrier layer **42** and the inorganic insulating film **43B** may each include the insulating film **55** constituting the bottom surface of the step portion **42A** or **43C** and the insulating film **56** constituting the side face of the step portion **42A** or **43C**, as illustrated in FIG. **16**, for example. In this case, the insulating film **55** may include an inorganic material of which etching rate is lower than that of the insulating film **56** in terms of a predetermined etching gas or a predetermined etchant. For example, in the case of dry etching using a fluorine-containing gas, a silicon nitride film has a larger etching rate than a silicon oxide film. Thus, for example, the insulating film **56** includes silicon nitride (SiN_x), and the insulating film **55** includes silicon oxide (SiO_x). In such a case, according to the foregoing embodiments and Modification Examples A, B, and C, the insulating film **55** serve as an etching stop layer when the UC barrier layer **42** and the inorganic insulating film **43B** are selectively etched. As a result, it is possible to precisely control the height of the step portions **42A** and **43C** in the manufacturing process.

Modification Example E

[0109] FIG. **17** illustrates a modification example of the cross-sectional configuration illustrated in FIG. **4**. FIG. **18** illustrates a modification example of the cross-sectional configuration illustrated in FIG. **12**. In the foregoing embodiments and Modification Example B, the resin layer **46** may be formed so as to be in contact with the entire surface of the inorganic insulating film **45**, to be in contact with from a portion of the inorganic insulating film **43B** in contact with the end portion of the inorganic insulating film **45** to the step portion **43C**, and to cover the step portion **43C**, as illustrated in FIGS. **17** and **18**, for example. In this case, the end portion of the resin layer **46** is formed so as to be in contact with the portion of the inorganic insulating film **43B** in the region between the end portion of the inorganic insulating film **43B** and the step portion **43C**. The step portion **43D** is formed in the portion where the end portion of the resin layer **46** is in contact with the surface of the inorganic insulating film **43B**. Such a structure is formed by, for example, selectively etching the TFT layer **43** using a film different from the polarization plate **47** as a mask to form the step portion **43C**, and then selectively etching the resin layer **46** using the polarization plate **47** having a size enough to cover the step portion **43C** as a mask to form the step portion **43D**. [0110] Accordingly, even if a crack generated in the end portion of the inorganic insulating film **43B** expands over the step portion **43D**, the resin layer **46** helps prevent the crack from expanding through the portions of the inorganic insulating films **43B** and **45** covered with the resin layer **46**.

As a result, it is possible to suppress the occurrence of a display failure, such as a dark spot, due to the crack generated in the inorganic insulating film 43B.

Modification Example F

[0111] FIG. 19 illustrates a modification example of the cross-sectional configuration illustrated in FIG. 14. In Modification Example C described above, the resin layer 54 may be formed so as to cover the entire surface of the region of the UC barrier layer 42 opposed to the organic electroluminescent elements 44A and to cover the step portion 42A of the UC barrier layer 42, as illustrated in FIG. 19, for example. In this case, the end portion of the resin layer 54 is formed so as to be in contact with the portion of the UC barrier layer 42 in the region between the end portion of the UC barrier layer 42 and the step portion 42A. The step 42B is formed in the portion where the end portion of the resin layer 54 is in contact with the surface of the UC barrier layer 42. Such a structure is formed by, for example, selectively etching the UC barrier layer 42 using a layer different from the polarization plate 47 to form the step portion 42A, and then selectively etching the resin layer 54 using the polarization plate 47 having a size enough to cover the step portion 42A as a mask to form the step 42B.

[0112] Accordingly, even if a crack generated in the end portion of the UC barrier layer 42 expands over the step portion 42A, the resin layer 54 helps prevent the crack from expanding through the portion of the UC barrier layer 42 covered with the resin layer 54. As a result, it is possible to suppress the occurrence of a display failure, such as a dark spot, due to the crack generated in the UC barrier layer 42.

[0113] Further, the disclosure may take the following configurations, for example.

[0114] (1) A display panel including: [0115] a flexible substrate; [0116] a plurality of self-luminescent elements provided on a first main face of the flexible substrate; [0117] a plurality of thin film transistor (TFT) circuits provided between the first main face and the plurality of self-luminescent elements and driving the self-luminescent elements; [0118] a first inorganic film provided between the plurality of TFT circuits and the plurality of self-luminescent elements, covering the TFT circuits, and having a step portion, the step portion being a thinned portion of the first inorganic film opposed to an end portion of the flexible substrate; [0119] a second inorganic film covering the self-luminescent elements; and [0120] a resin layer covering the second inorganic film and covering at least a portion of the first inorganic film in contact with an end portion of the second inorganic film.

[0121] (2) The display panel according to (1), in which an end portion of the resin layer is formed on the step portion.

[0122] (3) The display panel according to (1), in which the resin layer is formed so as to cover the step portion.

[0123] (4) The display panel according to any one of (1) to (3), further including: [0124] a plurality of mounting terminals electrically coupled to the plurality of TFT circuits; and [0125] flexible printed circuits (FPC) joined to the plurality of mounting terminals, in which, [0126] the step portion is formed in the first inorganic film at a position not opposed to the mounting terminals.

[0127] (5) A display panel including: [0128] a flexible substrate; [0129] a plurality of self-luminescent elements provided on a first main face of the flexible substrate; [0130] a plurality of thin film transistor (TFT) circuits provided between the first main face and the plurality of self-luminescent elements and driving the self-luminescent elements; [0131] an inorganic film provided between the flexible substrate and the plurality of TFT circuits, covering the first main face, and having a step portion, the step portion being a thinned portion of the inorganic film opposed to an end portion of the flexible substrate; and [0132] a resin layer covering a portion of the inorganic film other than the thinned portion.

[0133] (6) The display panel according to (5), in which an end portion of the resin layer is formed on the step portion.

[0134] (7) The display panel according to (5), in which the resin layer is formed so as to cover the

step portion.

[0135] (8) The display panel according to any one of (5) to (7), further including: [0136] a plurality of mounting terminals electrically coupled to the plurality of TFT circuits; and [0137] flexible printed circuits joined to the plurality of mounting terminals, in which [0138] the step portion is formed in the inorganic film at a position not opposed to the mounting terminals.

[0139] (9) A display apparatus including: [0140] a display panel; and [0141] a driver that drives the display panel, in which [0142] the display panel includes [0143] a flexible substrate, [0144] a plurality of self-luminescent elements provided on a first main face of the flexible substrate; [0145] a plurality of thin film transistor (TFT) circuits provided between the first main face and the plurality of self-luminescent elements and driving the self-luminescent elements, [0146] a first inorganic film provided between the plurality of TFT circuits and the plurality of self-luminescent elements, covering the TFT circuits, and having a step portion, the step portion being a thinned portion of the first inorganic film opposed to an end portion of the flexible substrate; [0147] a second inorganic film covering the self-luminescent elements; and [0148] a resin layer covering the second inorganic film and covering at least a portion of the first inorganic film in contact with an end portion of the second inorganic film.

[0149] (10) The display apparatus according to (9), further including: [0150] a plurality of mounting terminals electrically coupled to the plurality of TFT circuits; and [0151] flexible printed circuits (FPC) joined to the plurality of mounting terminals and the driver, in which [0152] the step portion is formed in the first inorganic film at a position not opposed to the mounting terminals.

[0153] (11) A display apparatus including: [0154] a display panel; and [0155] a driver that drives the display panel, in which [0156] the display panel includes [0157] a flexible substrate, [0158] a plurality of self-luminescent elements provided on a first main face of the flexible substrate, [0159] a plurality of thin film transistor (TFT) circuits provided between the first main face and the plurality of self-luminescent elements and driving the self-luminescent elements, [0160] an inorganic film provided between the flexible substrate and the plurality of TFT circuits, covering the first main face, and having a step portion, the step portion being a thinned portion of the inorganic film opposed to an end portion of the flexible substrate, and [0161] a resin layer covering a portion of the inorganic film other than the thinned portion.

[0162] (12) The display apparatus according to (11), further including: [0163] a plurality of mounting terminals electrically coupled to the plurality of TFT circuits; and [0164] flexible printed circuits (FPC) joined to the plurality of mounting terminals and the driver, in which [0165] the step portion is formed in the inorganic film at a position not opposed to each of the mounting terminals.

[0166] The present application claims priority based on Japanese Patent Application No. 2019-001931 filed with the Japan Patent Office on Jan. 9, 2019, the entire contents of which are incorporated herein by reference.

[0167] It should be understood that those skilled in the art would make various modifications, combinations, sub-combinations, and alterations depending on design requirements and other factors, and they are within the scope of the attached claims or the equivalents thereof.

Claims

1. A display panel, comprising: a flexible substrate including a display region and a peripheral region, the peripheral region being positioned in a periphery of the display region; a plurality of self-luminescent elements on a first main face of the display region of the flexible substrate; a plurality of thin film transistor (TFT) circuits between the first main face and the plurality of self-luminescent elements for driving the plurality of self-luminescent elements; a first laminated inorganic film between the first main face and the plurality of self-luminescent elements, the first laminated inorganic film including a step portion which is a thinned portion of the first laminated inorganic film and disposed in the peripheral region of the flexible substrate; a second inorganic

film covering the plurality of self-luminescent elements; and a resin layer overlapping the second inorganic film and overlapping at least a portion of the first laminated inorganic film in contact with an end portion of the second inorganic film.

2. The display panel according to claim 1, wherein the step portion includes a bottom surface and a side surface, with the bottom surface and the side surface being comprised of different materials.

3. The display panel according to claim 2, wherein the bottom surface includes a surface parallel to the first main face.

4. The display panel according to claim 2, wherein the bottom surface consists of a portion of the first laminated inorganic film closest to the flexible substrate.

5. The display panel according to claim 2, wherein an etching rate of a fluorine-containing gas of a bottom material of the bottom surface is lower than a side material of the side surface.

6. The display panel according to claim 1, wherein the first laminated inorganic film is selected from at least one of silicon oxide (SiO_x), silicon nitride (SiN_x), silicon nitride oxide (SiN_xO_y), titanium oxide (TiO_x), and aluminum oxide (Al_xO_y).

7. The display panel according to claim 1, wherein the resin layer contacts a bottom surface of the first laminated inorganic film.

8. The display panel according to claim 1, wherein the first laminated inorganic film overlaps the plurality of TFT circuits.
