

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12401078
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Ishitobi; Hideki

Method for manufacturing electric vehicle battery case and electric vehicle battery case

Abstract

A method for manufacturing an electric vehicle battery case includes: preparing a frame configured to define a through space inside and a flat plate made of resin; superposing and disposing the flat plate on the frame; and applying pressure to the flat plate from an opposite side from the frame to press the flat plate against the frame to cause the flat plate to swell in the through space, thereby deforming the flat plate into a tray having a bathtub shape including a bottom wall and a peripheral wall provided at a peripheral edge of the bottom wall and configured to define an opening portion, and joining by press-fitting the tray to the frame.

Inventors:	Ishitobi; Hideki (Kobe, JP)
Applicant:	KOBE STEEL, LTD. (Hyogo, JP)
Family ID:	1000008777438
Assignee:	KOBE STEEL, LTD. (Hyogo, JP)
Appl. No.:	17/753729
Filed (or PCT Filed):	September 04, 2020
PCT No.:	PCT/JP2020/033653
PCT Pub. No.:	WO2021/070533
PCT Pub. Date:	April 15, 2021

Prior Publication Data

Document Identifier	Publication Date
US 20220344752 A1	Oct. 27, 2022

Foreign Application Priority Data

Publication Classification

Int. Cl.: **H01M50/121** (20210101); **B29C70/18** (20060101); **B29C70/46** (20060101); **B29K101/12** (20060101); **B29K105/08** (20060101); **B29L31/00** (20060101); **B60L50/64** (20190101); **H01M50/242** (20210101); **H01M50/249** (20210101)

U.S. Cl.:

CPC **H01M50/121** (20210101); **B29C70/18** (20130101); **B29C70/46** (20130101); **B60L50/64** (20190201); **H01M50/242** (20210101); **H01M50/249** (20210101); B29K2101/12 (20130101); B29K2105/0863 (20130101); B29L2031/7146 (20130101); H01M2220/20 (20130101)

Field of Classification Search

CPC: H01M (50/207); H01M (50/227); H01M (50/249); H01M (50/242); B60L (50/64); B29C (70/18); B29C (70/46); B29K (2105/0863); B29K (2101/12); B29L (2031/7146)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2010/0136402	12/2009	Hermann et al.	N/A	N/A
2010/0273034	12/2009	Hermann et al.	N/A	N/A
2011/0143179	12/2010	Nakamori	429/99	H01M 50/271
2011/0174556	12/2010	Hermann et al.	N/A	N/A
2012/0160088	12/2011	Rawlinson	N/A	N/A
2012/0160583	12/2011	Rawlinson	N/A	N/A
2012/0161429	12/2011	Rawlinson et al.	N/A	N/A
2012/0161472	12/2011	Rawlinson et al.	N/A	N/A
2012/0231306	12/2011	Herron et al.	N/A	N/A
2012/0237803	12/2011	Mardall et al.	N/A	N/A
2012/0301765	12/2011	Loo et al.	N/A	N/A
2012/0308858	12/2011	Hermann et al.	N/A	N/A
2012/0308859	12/2011	Hermann et al.	N/A	N/A
2012/0312615	12/2011	Rawlinson	N/A	N/A
2013/0088044	12/2012	Charbonneau et al.	N/A	N/A
2013/0088045	12/2012	Charbonneau et al.	N/A	N/A
2013/0153317	12/2012	Rawlinson et al.	N/A	N/A
2013/0252059	12/2012	Choi	156/60	B29C 65/002
2014/0182958	12/2013	Rawlinson et al.	N/A	N/A
2014/0193683	12/2013	Mardall et al.	N/A	N/A
2014/0352886	12/2013	Choi et al.	N/A	N/A
2015/0239331	12/2014	Rawlinson et al.	N/A	N/A
2015/0255764	12/2014	Loo	429/149	H01M 50/249
2018/0334022	12/2017	Rawlinson et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
1249286	12/2001	EP	N/A
2004-314721	12/2003	JP	N/A
2010-207838	12/2009	JP	N/A
2011-124101	12/2010	JP	N/A
2012-212659	12/2011	JP	N/A
2013-133044	12/2012	JP	N/A
2013-133044	12/2012	JP	N/A
2013-201112	12/2012	JP	N/A
2015-170452	12/2014	JP	N/A
2017-226353	12/2016	JP	N/A

OTHER PUBLICATIONS

English translation of JP Publication 2013-133044, Jul. 2013. cited by examiner
International Search Report issued in PCT/JP2020/033653; mailed Nov. 10, 2020. cited by applicant
International Preliminary Report On Patentability and Written Opinion issued in PCT/JP2020/033653; mailed Apr. 21, 2022. cited by applicant

Primary Examiner: Raymond; Brittany L

Attorney, Agent or Firm: Studebaker Brackett PLLC

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS

(1) This is a national phase application in the United States of International Patent Application No. PCT/JP2020/033653 with an international filing date of Sep. 4, 2020, which claims priority of Japanese Patent Application No. 2019-187899 filed on Oct. 11, 2019 the contents of which are incorporated herein by reference.

TECHNICAL FIELD

(2) The present invention relates to a method for manufacturing an electric vehicle battery case and an electric vehicle battery case.

BACKGROUND ART

(3) An electric vehicle such as an electric car needs to mount with a large capacity battery in order to secure a sufficient cruising distance, and on the other hand, the electric vehicle is required to include a wide vehicle interior. In order to satisfy these requirements, in many electric cars, a large-capacity battery is stored in a battery case and mounted on the entire underfloor surface of the vehicle. Therefore, the electric vehicle battery case is required to have high sealing performance for preventing water from entering from a road surface or the like to prevent malfunctions of electronic components, and high collision strength is required to protect the internal battery.

(4) For example, JP 2017-226353 A discloses a battery case in which sealing performance is improved by using a tray obtained by forming a metal plate into a bathtub shape by cold press forming. In addition, JP 2012-212659 A discloses a battery case in which space efficiency and collision strength are improved by joining a bottom plate and a frame of the battery case by joining means such as welding.

SUMMARY

- (5) In the battery case of JP 2017-226353 A, since the metal plate is formed into a bathtub shape by cold press forming, a draft angle of a die (inclination of a side surface) and a ridgeline portion or a corner portion of a bottom portion need to be rounded, and space efficiency for mounting the battery cannot be improved. In addition, it is also necessary to additionally join a bathtub tray and a longitudinal frame being a frame by welding or the like.
- (6) In the battery case of JP 2012-212659 A, thermal deformation may occur along with joining means such as welding. Therefore, it is necessary to add an inspection step and a repair step regarding sealing accuracy, joining accuracy, and the like.
- (7) In an electric vehicle battery case and a method for manufacturing the same, the present invention has an object to secure sufficient sealing performance and to achieve simple and highly accurate joining.
- (8) A first aspect of the present invention provides a method for manufacturing an electric vehicle battery case, the method including: preparing a frame configured to define a space inside and a member to be formed made of resin; superposing and disposing the member to be formed on the frame; and applying pressure to the member to be formed from an opposite side from the frame to press the member to be formed against the frame to cause the member to be formed to swell in the space, thereby deforming the member to be formed into a tray having a bathtub shape including a bottom wall and a peripheral wall provided at a peripheral edge of the bottom wall and configured to define an opening portion, and integrating the tray with the frame.
- (9) According to this method, a member to be formed made of resin can be formed into a bathtub shaped tray and integrated with the frame at the same time. Since the member to be formed is formed into the bathtub shaped tray by pressurization, there is no seam in the tray, and high sealing performance can be secured. In addition, since forming of the member to be formed into a bathtub shape and joining by press-fitting of the member to be formed to the frame are simultaneously performed, the joining step can be simplified. Since the tray is integrated with the frame without welding, it is possible to achieve highly accurate joining without causing thermal deformation. Therefore, sufficient sealing performance of the battery case can be secured, and the tray obtained by forming the member to be formed into a bathtub shape and the frame can be simply and highly accurately joined.
- (10) The tray is obtained by forming a resin member to be formed into a bathtub shape. That is, the tray is made of resin. Making the tray made of resin allows the weight of the electric vehicle battery case to be further reduced as compared with the case where the tray is made of metal. In addition, since the member to be formed is made of resin, the degree of freedom of the shape of the tray is high.
- (11) The tray may further include a flange provided at a tip of the peripheral wall.
- (12) The resin constituting the member to be formed may have thermoplasticity. The member to be formed may be heated when pressure is applied to the member to be formed from an opposite side from the frame.
- (13) The heating the member to be formed may be performed by at least any one of heating the member to be formed itself and heating the frame.
- (14) The member to be formed may have a flat plate shape.
- (15) The method for manufacturing an electric vehicle battery case may further include primarily molding the member to be formed including a bottom wall, a peripheral wall provided at a peripheral edge of the bottom wall, and a flange provided at a tip of the peripheral wall.
- (16) According to this method, a member to be formed primarily molded into a shape similar to that of the tray, that is, a shape having a bottom wall, a peripheral wall, and a flange is used for deformation into the bathtub shaped tray, and for joining by press-fitting to the frame, due to application of pressure. That is, the deformation of the member to be formed into the tray is performed stepwise in two steps. Therefore, since the amount of strain applied to the member to be formed is reduced as compared with the case where only applying pressure to the flat plate shaped

member to be formed causes the member to be formed to be deformed into the tray and causes the tray to be joined by press-fitting to the frame, reduction in local wall thickness can be suppressed.

(17) The resin may be fiber-reinforced resin. The primary molding of the member to be formed may be injection molding.

(18) The resin may be fiber-reinforced resin. The primary molding of the member to be formed may be a hot press of SMC.

(19) The frame may be made of metal.

(20) The applying pressure to the member to be formed from the opposite side from the frame may be performed by a pressure forming method.

(21) By adopting the pressure forming method, omission of a draft angle (inclination of a side surface) which is difficult, for example, in the general cold press forming of metal and reduction in the roundness of the ridgeline portion or the corner portion are enabled, and the degree of freedom of the shape of the tray having a bathtub shape is increased. In addition, omitting the draft angle and reducing the roundness of the ridgeline portion allows the space efficiency of the tray to be improved and a battery having a larger capacity to be mounted. Here, the pressure forming method refers to a method of forming a member by gas or liquid pressure.

(22) The applying pressure to the member to be formed from the opposite side from the frame may include: preparing a hydraulic transfer elastic body configured to be elastically deformed using pressure of liquid, superposing and disposing the hydraulic transfer elastic body on the member to be formed superposed and disposed on the frame, and applying pressure to the member to be formed via the hydraulic transfer elastic body.

(23) According to this method, when the member to be formed is formed into a bathtub shape, liquid to which pressure is applied does not scatter or leak. Here, for example, the hydraulic transfer elastic body may have a structure in which only a lower surface of a metal chamber containing a liquid is closed with a rubber plate. The rubber plate is elastically deformed by adjusting the pressure of the liquid, and forming can be performed without the liquid coming into direct contact with the member to be formed. If the hydraulic transfer elastic body is not used in the pressure forming method, since the member to be formed is directly deformed by a fluid held at a high pressure, it is necessary to strongly constrain the outer edge portion of the member to be formed so that the fluid does not scatter or leak to the outside. However, when the hydraulic transfer elastic body is used, since the liquid to which the force is applied does not scatter or leak, the constraint force on the outer edge portion of the member to be formed can be reduced.

Therefore, when the member to be formed is formed into a bathtub shape, the material amount flowing from the outer edge portion to the inside can be increased, and stable machining can be achieved by suppressing cracking or the like of the member to be formed. In addition, since it is not necessary to completely seal the outer edge portion of the member to be formed, maintenance of the die and the pressing machine for constraining the outer edge portion becomes easy, and productivity can be improved.

(24) When the applying pressure to the member to be formed from the opposite side from the frame to deform the member to be formed into the tray is performed, negative angle forming of forming a negative angle at least partially from the bottom wall toward the opening portion of the tray may be performed.

(25) According to this method, since the negative angle is formed when the member to be formed is formed into the tray having a bathtub shape, it is possible to prevent the joining by press-fitting of the tray to the frame from being released by the negative angle portions. Here, the negative angle is a term often used in the forming field using a die, and indicates that the die draft angle in the formed member is less than zero (negative). Therefore, the joining strength between the frame and the tray having a bathtub shape is increased by the negative angle forming. In particular, the negative angle forming is forming peculiar to a pressure forming method because in cold press forming requiring a draft angle using a normal die, there is a problem that a cam mechanism needs

to be added and a die structure becomes complicated.

(26) The frame may have a negative angle portion in which a negative angle is formed in advance. The negative angle forming may be performed by pressing the member to be formed against the negative angle portion of the frame when the applying pressure to the member to be formed from the opposite side from the frame to deform the member to be formed into the tray is performed.

(27) According to this method, by the negative angle portion in the frame, the negative angle forming can be easily and reliably performed.

(28) The negative angle forming may be performed by integrally deforming the frame and the member to be formed to form the negative angle when the applying pressure to the member to be formed from the opposite side from the frame to deform the member to be formed into the tray is performed.

(29) According to this method, since the member to be formed and the frame are integrally deformed to form a negative angle, it is not necessary to provide the negative angle portion in advance to the frame. Therefore, negative angle forming can be easily performed.

(30) A second aspect of the present invention provides an electric vehicle battery case including: a frame made of metal configured to define a space inside; and a tray made of resin and having a bathtub shape, the tray including a bottom wall positioned in the space, a peripheral wall provided around the bottom wall and configured to define an opening portion on an opposite side from the bottom wall, and a flange provided at a tip of the peripheral wall, the tray being joined by press-fitting to the frame.

(31) According to this configuration, since the tray has a bathtub shape and has no seam, the sealing performance can be improved, and since the frame and the tray are integrated without being welded, highly-accurate joining is achieved without causing dimensional change due to thermal deformation. In addition, since the tray is made of resin, the weight of the electric vehicle battery case can be further reduced as compared with the case where the tray is made of metal.

Furthermore, since the tray is made of resin, the degree of freedom of the shape of the tray is high.

(32) A negative angle portion in which a negative angle directed at least partially inward from the bottom wall, toward an opening portion, of the tray is formed may be provided.

(33) Since the negative angle portion is formed in the tray, it is possible to prevent the joining by press-fitting from disconnection and to improve the strength of the electric vehicle battery case.

(34) The tray may be made of fiber-reinforced resin.

(35) By setting the tray as made of fiber-reinforced resin, it is possible to improve the strength of the tray while securing the weight reduction in the tray.

(36) The frame may be made of an aluminum alloy extruded product, an aluminum alloy cast product, a magnesium alloy extruded product, a magnesium alloy cast product, or a combination thereof.

(37) Since the frame is made of an aluminum-based or magnesium-based material, it is possible to reduce the weight of the frame while securing strength.

(38) The frame may be made of a steel plate roll form material, a steel plate press component, or a combination thereof.

(39) By forming the frame with a steel member, it is possible to increase the strength of the frame while suppressing the cost.

(40) The frame may include a cross member.

(41) Since the frame includes the cross member, the strength of the electric vehicle battery case can be improved. In particular, the cross member can improve strength against collision from the side of the vehicle.

(42) According to the present invention, in an electric vehicle battery case and a method for manufacturing the same, sufficient sealing performance can be secured and simple and highly accurate joining can be achieved.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) FIG. 1 is a schematic side view of an electric car mounting an electric vehicle battery case according to a first embodiment of the present invention;
- (2) FIG. 2 is a schematic cross-sectional view of an electric vehicle battery case taken along a vehicle width direction;
- (3) FIG. 3 is a perspective view of an electric vehicle battery case;
- (4) FIG. 4 is an exploded perspective view of an electric vehicle battery case;
- (5) FIG. 5 is a cross-sectional view taken along line V-V in FIG. 3;
- (6) FIG. 6 is a cross-sectional view taken along line VI-VI in FIG. 3;
- (7) FIG. 7 is a cross-sectional view taken along line VII-VII in FIG. 3;
- (8) FIG. 8 is a schematic cross-sectional view for illustrating the method for manufacturing an electric vehicle battery case according to the first embodiment;
- (9) FIG. 9 is a schematic cross-sectional view for illustrating the method for manufacturing an electric vehicle battery case according to the first embodiment;
- (10) FIG. 10 is a schematic cross-sectional view for illustrating the method for manufacturing an electric vehicle battery case according to the first embodiment;
- (11) FIG. 11 is an enlarged view of a portion XI in FIG. 10;
- (12) FIG. 12 is a cross-sectional view similar to FIG. 11 showing a first alternative of the first embodiment;
- (13) FIG. 13 is a cross-sectional view similar to FIG. 11 showing a second alternative of the first embodiment;
- (14) FIG. 14 is a cross-sectional view similar to FIG. 11 showing a third alternative of the first embodiment;
- (15) FIG. 15 is a cross-sectional view similar to FIG. 11 showing a fourth alternative of the first embodiment;
- (16) FIG. 16 is a cross-sectional view similar to FIG. 5 showing a primary molded member in a second embodiment of the present invention;
- (17) FIG. 17 is a cross-sectional view similar to FIG. 6 showing a primary molded member in the second embodiment;
- (18) FIG. 18 is a cross-sectional view similar to FIG. 7 showing a primary molded member in the second embodiment;
- (19) FIG. 19 is a schematic cross-sectional view for illustrating a pressure forming step in the second embodiment;
- (20) FIG. 20 is a perspective view showing a state in which a constraining die used in a method for manufacturing an electric vehicle battery case according to a third embodiment of the present invention is attached to a frame;
- (21) FIG. 21 is an exploded perspective view of the constraining die used in the method for manufacturing an electric vehicle battery case according to the third embodiment;
- (22) FIG. 22 is a schematic cross-sectional view for illustrating the method for manufacturing an electric vehicle battery case according to the third embodiment;
- (23) FIG. 23 is a schematic cross-sectional view for illustrating the method for manufacturing an electric vehicle battery case according to the third embodiment;
- (24) FIG. 24 is a schematic cross-sectional view for illustrating the method for manufacturing an electric vehicle battery case according to the third embodiment;
- (25) FIG. 25 is a schematic cross-sectional view for illustrating the method for manufacturing an electric vehicle battery case according to a modification of the third embodiment; and
- (26) FIG. 26 is a schematic cross-sectional view for illustrating a method for manufacturing an

electric vehicle battery case according to a fourth embodiment of the present invention.

MODE FOR CARRYING OUT THE INVENTION

First Embodiment

(27) Referring to FIG. 1, an electric vehicle **1** is a vehicle that travels by driving a motor by electric power supplied from a battery **30**. The electric vehicle **1** is a vehicle that travels by electric power, and may be, for example, an electric car, a plug-in hybrid vehicle, or the like. The type of the vehicle is not particularly limited, and may be a passenger car, a truck, a maintenance vehicle, other mobility, or the like. Hereinafter, a case where the electric vehicle **1** is a passenger car type electric car will be taken as an example and described.

(28) The electric vehicle **1** mounts a motor, a high-voltage apparatus, and the like (not shown) in the vehicle body front portion **10**. In addition, the electric vehicle **1** mounts an electric vehicle battery case **100** (hereinafter, also simply referred to as a battery case **100**) in which a battery **30** is stored in substantially the entire underfloor space of the vehicle interior R of the vehicle body central portion **20**. It should be noted that in FIG. 1, the front-rear direction of the electric vehicle **1** is represented by the X direction, and the height direction is represented by the Z direction. The same notation also applies to the following drawings, and the vehicle width direction is represented by the Y direction in FIG. 2 and subsequent drawings.

(29) Referring to FIG. 2, the battery case **100** is disposed inside a pair of rocker members **200** being framework members in the vehicle width direction, and is supported by these rocker members **200**. Each rocker member **200** extends in the vehicle front-rear direction below the end portions in the vehicle width direction of the electric vehicle **1** (see FIG. 1). The rocker member **200** is formed by bonding a plurality of metal plates, and has a function of protecting the vehicle interior R and the battery case **100** against impact from the side of the electric vehicle **1**.

(30) Referring also to FIGS. 3 to 7, the battery case **100** includes a frame **110** that defines a through hole or a through space TH being an example of a space inside, a tray **120** having a bathtub shape, and a top cover **130** and an under cover **140** disposed so as to sandwich them from above and below.

(31) The frame **110** is a frame-shaped member forming the framework of the battery case **100**. The frame **110** is made of, for example, an aluminum alloy extruded product, an aluminum alloy cast product, a magnesium alloy extruded product, a magnesium alloy cast product, or a combination thereof. Since the frame **110** is made of an aluminum-based or magnesium-based material, it is possible to reduce the weight of the frame while securing strength. In particular, the frame **110** can be manufactured by joining a plurality of extruded hollow members made of a 6000 series aluminum alloy by arc welding. In this case, the aluminum alloy may be 7000 series.

(32) The frame **110** may be a steel plate roll form material, a steel plate press component, or a combination thereof. By forming the frame **110** with a steel member, it is possible to increase the strength of the frame while suppressing the cost.

(33) When the frame **110** is manufactured by joining a plurality of members, means suitable for materials such as friction stir welding (FSW), laser welding, electron beam welding, resistance spot welding, self piercing rivet (SPR), and Flow Drill Screw (FDS) can be adopted in addition to the arc welding described above.

(34) The frame **110** in the present embodiment includes a frame-shaped body **111** having a rectangular frame shape in plan view, and three cross members **112** extending in the vehicle width direction so as to cross the through space TH in the lower part of the frame-shaped body **111**. It should be noted that in the present embodiment, the frame **110** having the through space TH will be described as an example, but the shape of the frame **110** is not particularly limited. For example, the frame **110** may define a hollow portion having a recessed shape or a bottomed shape as a space replacing the through space TH.

(35) The frame-shaped body **111** includes side walls **111c** and **111d** extending in the vehicle front-rear direction, and a front wall **111a** and a rear wall **111b** connecting the side walls and extending in

the vehicle width direction. As shown in FIGS. 6 and 7, the outer contours of the side walls **111c** and **111d** are substantially L-shaped in a cross section perpendicular to the vehicle front-rear direction. The inside of each of the side walls **111c** and **111d** is partitioned into a plurality of chambers extending in the longitudinal direction to have a hollow shape. As shown in FIG. 5, the outer contours of the front wall **111a** and the rear wall **111b** have a quadrangular tubular shape in a cross section perpendicular to the vehicle width direction, and each of the insides of the front wall **111a** and the rear wall **111b** is also similarly partitioned into a plurality of chambers extending in the longitudinal direction to have a hollow shape. The outer contours of the side walls **111c** and **111d** may have a shape other than the L-shape, such as a quadrangular tubular shape, in a cross section perpendicular to the vehicle front-rear direction. In addition, the side walls **111c** and **111d** may be solid. The outer contours of the front wall **111a** and the rear wall **111b** may have a shape other than a quadrangular tubular shape, such as an L shape, in a cross section perpendicular to the vehicle width direction. In addition, the front wall **111a** and the rear wall **111b** may be solid.

(36) The three cross members **112** are provided at substantially equal intervals in parallel with the front wall **111a** and the rear wall **111b**, and each of the three cross members **112** connects the side wall **111c** and the side wall **111d**. The cross member **112** has a function of improving the strength of the battery case **100**. In particular, the cross member **112** can improve strength against collision from the side of the electric vehicle **1** (see FIG. 1). However, the cross member **112** is not an essential configuration, and may be omitted as necessary. In addition, also in the case of installing the cross member **112**, a mode thereof is not particularly limited, and the shape, arrangement, number, and the like can be optionally set.

(37) The tray **120** is made of thermoplastic resin. The tray **120** may be made of a thermoplastic resin such as polyethylene or polypropylene containing no reinforcement fiber. In addition, the tray **120** may be made of thermoplastic fiber-reinforced resin. More specifically, the thermoplastic fiber-reinforced resin that can be adopted as the material of the tray **120** includes GFRP (the reinforcement fiber is a glass fiber), CFRP (the reinforcement fiber is a carbon fiber), and CNFRP (the reinforcement fiber is a cellulose nanofiber). By setting the tray **120** as made of a fiber-reinforced resin, it is possible to improve the strength of the tray **120** while securing the weight reduction in the tray **120**.

(38) The tray **120** includes a bottom wall **120a**, a peripheral wall **120c** that defines an opening portion **120b** on the opposite side from the bottom wall **120a** provided on the peripheral edge of the bottom wall **120a**, that is, on the tip side, and a flange **120d** that extends in the horizontal direction (X, Y directions) and spreads outward provided at the tip of the peripheral wall **120c**. That is, the tray **120** has a bathtub shape. The battery **30** is housed in a housing portion **120e** being a space surrounded by the bottom wall **120a** and the peripheral wall **120c**. The bottom wall **120a** is provided with a projecting portion **120f** projecting toward the opening portion **120b** and having a shape complementary to the cross member **112**.

(39) Referring to FIGS. 2, 3, and 5 to 7, the tray **120** is joined by press-fitting to the frame **110** by a pressure forming method to be integrated with the frame **110** as described in detail below.

Specifically, the bottom wall **120a** of the tray **120** is positioned in the lower part of the through space TH, and the outer surface of the peripheral wall **120c** of the tray **120** is in close contact with or in pressure contact with the inner surface of the frame-shaped body **111**. In addition, a lower surface of the projecting portion **120f** is in close contact with or in pressure contact with the cross member **112**. The flange **120d** of the tray **120** is placed on the upper surface of the frame-shaped body **111**.

(40) Referring to FIG. 2, the opening portion **120b** of the tray **120** is closed by the top cover **130**. In other words, the housing portion **120e** in which the battery **30** is housed is a closed space by the bottom wall **120a** of the tray **120**, the peripheral wall **120c** of the tray **120**, and the top cover **130**. The top cover **130** and the flange **120d** of the tray **120** are jointly fastened and fixed to the frame-shaped body **111** of the frame **110** by a screw. Above the top cover **130**, a floor panel **300**

constituting a floor surface of the vehicle interior R and a floor cross member **400** extending in the vehicle width direction in the vehicle interior R are disposed. In addition, an under cover **140** is disposed below the tray **120**. The under cover **140** is screwed to the frame **110** and supports the tray **120** from below. The top cover **130** and the under cover **140** may be fastened to other members by a method other than a screw, such as a rivet, a bolt, or an adhesive.

(41) Since the tray **120** has a bathtub shape and has no seam, the sealing performance can be improved, and since the frame and the tray are integrated by joining by press-fitting by a pressure forming method without being welded, highly-accurate joining is achieved without causing dimensional change due to thermal deformation. In addition, since the tray **120** is made of resin as described above, the weight of the electric vehicle battery case **1** can be further reduced as compared with the case where the tray **120** is made of metal. Furthermore, since the tray **120** is made of resin, the degree of freedom of the shape of the tray is high.

(42) Referring to FIGS. **5** to **7**, since the tray **120** is joined by press-fitting by a pressure forming method, omission of a draft angle (inclination of the peripheral wall **120c**) which is difficult, for example, in the cold press forming of metal and reduction in the roundness of the ridgeline portion or the corner portion are enabled, and it is possible to form the tray **120** having any shape. Specifically, in the case of the present embodiment, all of the peripheral walls **120c** are substantially orthogonal to the bottom wall **120a**, and the draft angle θ is 0 degrees. In addition, in the case of the present embodiment, the radius r of each of the ridgeline portion **120g** and the corner portion **120h** is about 1 mm to 20 mm, except for the portion where the round shape is formed of the inner upper portion of the frame-shaped body **111** of the frame **120**. As described above, omitting the draft angle θ in the tray **120** and reducing the roundness of the ridgeline portion **120g** and the corner portion **120h** allows the space efficiency of the battery case **100** to be improved and the battery **30** having a larger capacity to be mounted.

(43) Next, a method for manufacturing the battery case **100** of the present embodiment will be described with reference to FIGS. **8** to **11**.

(44) Referring to FIG. **8**, a flat plate (member to be machined) **150** made of thermoplastic resin, to serve as a tray **120** in a finished product, is prepared. Examples of a method for manufacturing the flat plate **150** include the following. First, in the case of a thermoplastic resin containing no reinforcement fiber, or GFRP, injection molding using pellets can be adopted. In the case of GFRP or CFRP (short fiber), hot pressing using sheet molding compound (SMC) can be adopted. Furthermore, in the case of CFRP (continuous fiber), resin transfer molding (RTM) using a woven fabric of reinforcement fibers, and a resin, or prepreg compression (PCM) of a prepreg sheet can be adopted.

(45) Next, referring to FIGS. **9** to **11**, the frame **120** is placed on a table **55** having a flat upper surface. In addition, the flat plate **150** is superposed and disposed on the frame **120** placed on the table **55**. In this state, pressure is applied to the flat plate **150** from the opposite side from the frame **110** to press the flat plate **150** against the frame **110**, thereby causing the flat plate **150** to swell into the through space TH. This swelling deforms the flat plate **150** into a bathtub shaped tray **120** including a bottom wall **120a**, a peripheral wall **120c**, and a flange **120d**. The tray **120** is joined by press-fitting to the frame **120** when being deformed from the flat plate **150** by pressurization. This integrates the tray **120** and the frame **110** as most clearly shown in FIGS. **5** to **7**.

(46) When pressure is applied to the flat plate **150** from the opposite side from the frame **110**, the flat plate **150** is heated. Since the flat plate **150** has thermoplasticity, plasticity is improved by heating. As a result, the flat plate **150** can be more reliably deformed into a desired bathtub shape by applying pressure. Examples of a method for heating the flat plate **150** include the following. First, hot air may be blown onto one or both of the flat plate **150** and the frame **110**. The flat plate **150** and the frame **110** may be housed together with the table **55** in a heating furnace heated to a high temperature by a heater. Furthermore, the frame **110** may be heated by electromagnetic induction.

(47) In the present embodiment, pressurization of the flat plate **150** is performed by a pressure forming method. Here, the pressure forming method refers to a method of forming a member by gas or liquid pressure. In the present embodiment, in the pressure forming method, the hydraulic transfer elastic body **50** that is elastically deformable using the pressure of the liquid is used. Although not shown in detail, the hydraulic transfer elastic body **50** may have a structure in which only a lower surface of a metal chamber containing a liquid such as water or oil is closed with a rubber plate, for example. The rubber plate is elastically deformed by adjusting the pressure of the liquid, and forming can be performed without the liquid coming into direct contact with the flat plate **150**.

(48) Referring to FIG. **10**, when the pressurizing force of a pressing machine (not shown) is released after the flat plate **150** is deformed into the bathtub-shaped tray **120**, the hydraulic transfer elastic body **50** returns to a shape in the natural state. Therefore, the hydraulic transfer elastic body **50** can be easily removed from the inside of the tray **120**. After the hydraulic transfer elastic body **50** is removed, the battery case **100** is formed by joining the top cover **130** and the under cover **140** as shown in FIG. **2**.

(49) It should be noted that in the present embodiment, the front wall **11a**, the rear wall **11b**, and the side walls **11c** and **11d** have wall thicknesses of the upper portions set to be larger than those of the other portions. The upper portions of the front wall **11a**, the rear wall **11b**, and the side walls **11c** and **11d** are portions susceptible to force due to the forming described above, and the wall thicknesses of the portions are increased to prevent unintended deformation. In addition, the inner upper portions of the front wall **11a**, the rear wall **11b**, and the side walls **11c** and **11d** are formed in a round shape, which promotes the inflow of the material to the inside of the flat plate **150** in the forming.

(50) In the manufacturing method of the present embodiment, the resin flat plate **150** can be formed into the bathtub shaped tray **120** and integrated with the frame **110** at the same time. Since the flat plate **150** is formed into the bathtub shaped tray **120** by pressurization, there is no seam in the tray **120**, and high sealing performance can be secured. In addition, since forming of the flat plate **150** into a bathtub shape and joining by press-fitting of the flat plate **150** to the frame **110** are simultaneously performed, the joining step can be simplified. Since the tray **120** is joined by press-fitting to the frame **110** instead of welding, it is possible to achieve highly accurate joining without causing thermal deformation. Therefore, sufficient sealing performance of the battery case **100** can be secured, and the tray **120** obtained by forming the flat plate **150** into a bathtub shape and the frame **110** can be simply and highly accurately joined.

(51) By adopting the pressure forming method for pressurizing the flat plate **150**, omission of a draft angle θ which is difficult, for example, in the general cold press forming of metal and reduction in the roundness of the ridgeline portion **120g** and the corner portion **120h** are enabled, and the degree of freedom of the shape of the tray **120** having a bathtub shape is increased. In addition, omitting the draft angle θ and reducing the roundness of the ridgeline portion **120g** and the corner portion **120h** allows the space efficiency of the tray **120** to be improved and the battery **30** having a larger capacity to be mounted.

(52) By adopting a pressure forming method using a hydraulic transfer elastic body for pressurizing the flat plate **150**, a liquid to which pressure is applied does not scatter or leak. If the hydraulic transfer elastic body is not used in the pressure forming method, since the flat plate **150** is directly deformed by a fluid held at a high pressure, it is necessary to strongly constrain the outer edge portion of the flat plate **150** so that the fluid does not scatter or leak to the outside. However, when the hydraulic transfer elastic body is used, since the liquid to which the force is applied does not scatter or leak, the constraint force on the outer edge portion of the flat plate **150** can be reduced. Therefore, when the flat plate **150** is formed into a bathtub shape, the material amount flowing from the outer edge portion to the inside can be increased, and stable machining can be achieved by suppressing cracking or the like of the member to be formed. In addition, since it is not necessary

to completely seal the outer edge portion of the flat plate **150**, maintenance of the pressing machine becomes easy, and productivity can be improved.

(53) FIGS. **12** to **15** show modifications of the present embodiment. These modifications can also be applied to the second and third embodiments described below.

(54) In the modification shown in FIG. **12**, when the flat plate **150** is formed into the tray **120** having a bathtub shape, negative angle forming for at least partially forming a negative angle from the bottom wall **120a** toward the opening portion **120b** of the tray **120** is performed. Here, the negative angle is a term often used in the forming field using a die, and indicates that the die draft angle in the formed member is less than zero (negative). In this modification, the frame-shaped body **111** of the frame **110** having no negative angle portion in advance and the flat plate **150** are integrally deformed by pressurization from the hydraulic transfer elastic body **50** to form a negative angle, whereby negative angle forming is performed. Specifically, the inner surface of the frame-shaped body **111** is deformed outward for each chamber, the peripheral wall **120c** of the tray **120** is also deformed outward, and the negative angle portions **111e** and **120i** are formed.

(55) In the modification in FIG. **12**, since the negative angle portions **111e** and **120i** are formed when the flat plate **150** is formed into the tray **120** having a bathtub shape, it is possible to prevent the joining by press-fitting of the tray **120** to the frame **110** from being released by the negative angle portions **111e** and **120i**. Therefore, the joining strength between the frame **110** and the tray **120** having a bathtub shape is increased by the negative angle forming. In particular, the negative angle forming is forming peculiar to a pressure forming method because in cold press forming requiring a draft angle using a normal die, there is a problem that a cam mechanism needs to be added and a die structure becomes complicated.

(56) In the modifications in FIGS. **13** to **15**, the negative angle portion **111e** is formed in advance in the frame-shaped body **111** of the frame **110**. In this case, the negative angle forming is performed by pressing the flat plate **150** against the negative angle portion **111e** of the frame-shaped body **111** formed in advance. In the modification in FIG. **13**, a negative angle portion **111e** is provided as a recess at a position on the lower end side in the diagram of the inner surface of the frame-shaped body **111**. In the modification in FIG. **14**, a negative angle portion **111e** is provided as a recess at an intermediate position in the height direction in the diagram of the inner surface of the frame-shaped body **111**. In the modification in FIG. **15**, the inner surface of the frame-shaped body **111** is inclined toward the center of the frame **110**, thereby forming the negative angle portion **111e** as an inclined surface. Thus, by providing the negative angle portion **111e** in the frame-shaped body **111** of the frame **110** in advance, the negative angle forming can be easily and reliably performed. The negative angle portion may also be formed in the cross member **112**.

(57) In the following, second and third embodiments of the present invention will be described. In these embodiments, the structure of the battery case **100** to be finally manufactured is similar to that of the first embodiment except for the points to be particularly referred to. In addition, the method for manufacturing a battery case in these embodiments is also similar to that of the first embodiment except for the points to be particularly referred to.

Second Embodiment

(58) Referring to FIGS. **16** to **18**, in the method for manufacturing the battery case **100** according to the present embodiment, a primary molded article (member to be machined) **160** made of thermoplastic resin having a bathtub shape close to a tray **120** being a finished product is prepared. In the present embodiment, the primary molded article **160** includes a bottom wall **160a**, a peripheral wall **160b** provided at a peripheral edge of the bottom wall **160a**, and a flange **160c** provided at a tip of the peripheral wall **160b**. The draft angle θ_i of the primary molded article **160** is not 0 degrees unlike the draft angle θ (FIGS. **5** to **7**) of the tray **120** being a finished product. That is, in the tray **120** of the finished product, the peripheral wall **120c** is not inclined, whereas the peripheral wall **160b** of the primary molded article **160** is inclined. In addition, the radius r_i of the ridgeline portion **160d** and the corner portion **160e** of the primary molded article **160** is about 5 mm

to 70 mm, and is larger than the radius r (FIGS. 5 to 7) of the ridgeline portion **120g** and the corner portion **120h** in the tray **120** of the finished product.

(59) Examples of a method for manufacturing the primary molded article **160** include the following. First, in the case of a thermoplastic resin containing no reinforcement fiber, or GFRP, injection molding using pellets can be adopted. In the case of GFRP or CFRP (short fiber), hot pressing using SMC can be adopted. Furthermore, in the case of CFRP (continuous fiber), RTM using a woven fabric of reinforcement fibers, and a resin, or PCM of a prepreg sheet can be adopted.

(60) Referring to FIG. 19, the primary molded article **160** is superposed and disposed on the frame **110** so that the flange **160c** is disposed on the upper surface of the frame-shaped body **111** of the frame **110** and the bottom wall **160a** and the peripheral wall **160b** are positioned in the through space TH. Thereafter, while the primary molded article **160** is heated, pressure is applied to the primary molded article **160** from the opposite side from the frame **110** by a pressure forming method using the hydraulic transfer elastic body **50**, and the primary molded article **160** is pressed against the frame **110** to be caused to swell into the through space TH. The swelling deforms the primary molded article **160** into a tray **120** having a bathtub shape, and the tray **120** is joined by press-fitting to the frame **110** at the same time.

(61) In the present embodiment, the primary molded article **160** molded in advance into a shape similar to that of the tray **120** is used for deformation into the bathtub shaped tray **120**, and for joining by press-fitting to the frame **110**, due to application of pressure. That is, the deformation into the tray **120** is performed stepwise in two steps. Therefore, since the amount of strain applied to the primary molded article **160** is reduced as compared with the case where only applying pressure to the flat plate causes the flat plate to be deformed into the tray **120** and causes the tray **120** to be joined by press-fitting to the frame **110**, reduction in local wall thickness can be suppressed.

Third Embodiment

(62) Referring to FIGS. 20 and 21, in the present embodiment, a constraining die **60** that constrains the position of the frame **110** when the flat plate **150** is pressurized by the pressure forming method is used. The constraining die **60** can also be used when the target of pressurization by the pressure forming method is the primary molded article **160** of the second embodiment.

(63) The constraining die **60** has a shape complementary to that of the frame **110** and is disposed outside the frame **110**. The constraining die **60** includes a front constraining member **61** and a rear constraining member **62** that respectively support the front wall **111a** and the rear wall **111b**, and side constraining members **63** and **64** that respectively support the side walls **111c** and **111d**. The front constraining member **61**, the rear constraining member **62**, and the side constraining members **63** and **64** are combined to form a frame shape in plan view. The upper surface of the constraining die **60** has a two-step shape. Specifically, the upper surface of the constraining die **60** has a first surface **60a** aligned at substantially the same height as the upper surface of the frame **110** and a second surface **60b** provided one step higher than the upper surface of the frame **110**. The first surface **60a** and the second surface **60b** are connected by an inclined surface **60c**, and the second surface **60b** is disposed outside the first surface **60a** in plan view. In addition, the lower surfaces of the frame **110** and the constraining die **60** are aligned. Therefore, when the height dimensions of the frame **110** and the constraining die **60** are compared, the height of the constraining die **60** is set larger than the height of the frame **110**.

(64) In the method for manufacturing the battery case **100** of the present embodiment, in addition to the first embodiment, the constraining die **60** that constrains the movement of the frame **110** is further prepared, and the constraining die **60** is fixed and disposed outside the frame **110** in plan view (see FIG. 20). Thereafter, as shown in FIGS. 22 to 24, the flat plate **150** is deformed into a bathtub tray **120** and integrated with the frame **110** as in the first embodiment.

(65) Specifically, as shown in FIG. 22, the flat plate **150** is disposed on the constraining die **60**, and

as shown in FIG. 23, the flat plate **150** is pressurized via the hydraulic transfer elastic body **50**, whereby the first outer edge portion **150a** of the flat plate **150** (portion slightly inside the outermost edge portion) is supported by the frame **110**, and the second outer edge portion **150b** (outermost edge portion) on the outer side of the first outer edge portion **150a** is supported by the second surface **60b** of the constraining die **60**. Thus, the flat plate **150** is disposed so as to be bent so that the height decreases from the outside toward the inside, and the flat plate **150** is continuously pressurized from the state in which the flat plate **150** is bent in this manner, whereby the flat plate **150** can be deformed into the tray **120** having a bathtub shape, and can be stably joined by press-fitting to the frame **110**.

(66) According to the present embodiment, since the flat plate **150** is pressurized in a state where the flat plate **150** is bent so that the height decreases from the outside toward the inside, the amount of the material flowing into the inside of the flat plate **150** can be increased, and the roundness of the ridge line portion or the corner portion of the bottom portion **122a** of the tray **120** can be further reduced.

(67) In the modification of the third embodiment shown in FIG. 25, the shape of the constraining die **60** is changed. Specifically, the upper portion **60d** of the constraining die **60** in this modification is flat. In addition, the height H1 of the constraining die **60** is set to be the same as the height H2 of the frame **110**. In particular, when there is no problem in formability when the flat plate **150** is deformed into the tray **120** (see FIG. 3), by making the heights H1 and H2 of the constraining die **60** and the tray **120** the same as in this modification, the width of the flange **120d** (see FIG. 3) of the tray **120** can be made minimum necessary. As a result, the material yield of the resin flat plate **150** can be improved.

Fourth Embodiment

(68) As shown in FIG. 26, the constraining die **60** can be used when the primary molded article **160** (see FIGS. 16 to 18) made of the thermoplastic resin having the bathtub shape described in the second embodiment is deformed into the tray **120** (see FIG. 3) by the pressure forming method using the hydraulic transfer elastic body **50**. In this case, as in the modification (FIG. 25) of the above-described third embodiment, the heights H1 and H2 of the constraining die **60** and the tray **120** are set to be the same.

(69) In the cross-sectional views (FIGS. 2, 5 to 15, 19, and 22 to 26) showing the frame-shaped body **111** of the frame **120** referred to in the above description, a round shape is not shown except for the inner upper portion described above. However, all corner portions of the frame-shaped body **111** may have round shapes as appropriate.

Claims

1. A method for manufacturing an electric vehicle battery case, the method comprising: preparing a frame configured to define a space inside and a member to be formed made of resin; superposing and disposing the member to be formed on the frame; and applying pressure to the member to be formed from an opposite side from the frame to press the member to be formed against the frame to cause the member to be formed to swell in the space, thereby deforming the member to be formed into a tray having a bathtub shape including a bottom wall and a peripheral wall provided at a peripheral edge of the bottom wall and configured to define an opening portion, and integrating the tray with the frame.
2. The method for manufacturing an electric vehicle battery case according to claim 1, wherein the tray further includes a flange provided at a tip of the peripheral wall.
3. The method for manufacturing an electric vehicle battery case according to claim 1, wherein the resin constituting the member to be formed has thermoplasticity, the method further comprising heating the member to be formed when pressure is applied to the member to be formed from an opposite side from the frame.

4. The method for manufacturing an electric vehicle battery case according to claim 3, wherein the heating the member to be formed is performed by at least any one of heating the member to be formed itself and heating the frame.
5. The method for manufacturing an electric vehicle battery case according to claim 1, wherein the member to be formed has a flat plate shape.
6. The method for manufacturing an electric vehicle battery case according to claim 1, further comprising primarily molding the member to be formed including a bottom wall, a peripheral wall provided at a peripheral edge of the bottom wall, and a flange provided at a tip of the peripheral wall.
7. The method for manufacturing an electric vehicle battery case according to claim 6, wherein the resin is fiber-reinforced resin, and wherein the primary molding of the member to be formed is injection molding.
8. The method for manufacturing an electric vehicle battery case according to claim 6, wherein the resin is fiber-reinforced resin, and wherein the primary molding of the member to be formed is a hot press of SMC.
9. The method for manufacturing an electric vehicle battery case according to claim 1, wherein the frame is made of metal.
10. The method for manufacturing an electric vehicle battery case according to claim 1, wherein applying pressure to the member to be formed from an opposite side from the frame is performed by a pressure forming method.
11. The method for manufacturing an electric vehicle battery case according to claim 10, wherein the applying pressure to the member to be formed from the opposite side from the frame includes: preparing a hydraulic transfer elastic body configured to be elastically deformed using pressure of liquid, superposing and disposing the hydraulic transfer elastic body on the member to be formed superposed and disposed on the frame, and applying pressure to the member to be formed via the hydraulic transfer elastic body.
12. The method for manufacturing an electric vehicle battery case according to claim 1, wherein when the applying pressure to the member to be formed from the opposite side from the frame to deform the member to be formed into the tray is performed, negative angle forming of forming a negative angle at least partially from the bottom wall toward the opening portion of the tray is performed.
13. The method for manufacturing an electric vehicle battery case according to claim 12, wherein the frame has a negative angle portion in which a negative angle is formed in advance, and wherein the negative angle forming is performed by pressing the member to be formed against the negative angle portion of the frame when the applying pressure to the member to be formed from the opposite side from the frame to deform the member to be formed into the tray is performed.
14. The method for manufacturing an electric vehicle battery case according to claim 12, wherein the negative angle forming is performed by integrally deforming the frame and the member to be formed to form the negative angle when the applying pressure to the member to be formed from the opposite side from the frame to deform the member to be formed into the tray is performed.
15. An electric vehicle battery case comprising: a frame made of metal configured to define a space inside; and a tray made of resin and having a bathtub shape, the tray including a bottom wall positioned in the space, a peripheral wall provided around the bottom wall and configured to define an opening portion on an opposite side from the bottom wall, and a flange provided at a tip of the peripheral wall, the tray being integrated with the frame, wherein a negative angle portion in which a negative angle directed at least partially inward from the bottom wall toward an opening portion of the tray is provided.
16. The electric vehicle battery case according to claim 15, wherein the tray is made of fiber-reinforced resin.
17. The electric vehicle battery case according to claim 15, wherein the frame is made of an

aluminum alloy extruded product, an aluminum alloy cast product, a magnesium alloy extruded product, a magnesium alloy cast product, or a combination of them.

18. The electric vehicle battery case according to claim 15, wherein the frame is made of a steel plate roll form material, a steel plate press component, or a combination of them.

19. The electric vehicle battery case according to claim 15, wherein the frame includes a cross member.
