

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12408680
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Ryan; Justin et al.

Compounds and formulations for protective coatings

Abstract

The present disclosure relates to protective coatings e.g., on agricultural products, that can include a glycerophospholipid bilayer structure formed on the surface of the agricultural product.

Inventors: Ryan; Justin (Goleta, CA), Zhang; Stanley (Goleta, CA), Frazier; Charles Patrick (Goleta, CA)

Applicant: Apeel Technology, Inc. (Goleta, CA)

Family ID: 83688890

Assignee: Apeel Technology, Inc. (Goleta, CA)

Appl. No.: 17/940811

Filed: September 08, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230095677 A1	Mar. 30, 2023

Related U.S. Application Data

us-provisional-application US 63241991 20210908

Publication Classification

Int. Cl.: A23B7/154 (20060101); A23B2/775 (20250101); A23B7/16 (20060101); C07F9/09 (20060101)

U.S. Cl.:

CPC A23B7/154 (20130101); A23B2/775 (20250101); A23B7/16 (20130101); C07F9/091 (20130101); A23V2002/00 (20130101)

Field of Classification Search

CPC: A23B (7/154); A23B (7/16); A23L (3/3553); A23L (3/3526); C07F (9/091); A23V (2002/00)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
1016761	12/1911	Moore	N/A	N/A
1943468	12/1933	Bridgeman	N/A	N/A
2213557	12/1939	Tisdale et al.	N/A	N/A
2222000	12/1939	Schmidt	N/A	N/A
2223168	12/1939	Dombrow et al.	N/A	N/A
2275659	12/1941	Steinle et al.	N/A	N/A
2324448	12/1942	Gottlieb	N/A	N/A
2333887	12/1942	Redlinger	N/A	N/A
2342063	12/1943	Sells	N/A	N/A
2363232	12/1943	De Witt	N/A	N/A
2424952	12/1946	Handy	N/A	N/A
2470281	12/1948	Allingham	426/310	A23B 4/10
2472794	12/1948	Cothran	N/A	N/A
2657282	12/1952	Winkel	N/A	N/A
2697793	12/1953	Trump et al.	N/A	N/A
2744019	12/1955	Snyder	426/302	B65B 25/041
2857282	12/1957	Jansen	N/A	N/A
2866709	12/1957	Gerwe et al.	N/A	N/A
3189467	12/1964	Kalmar	N/A	N/A
3208951	12/1964	Berger et al.	N/A	N/A
3232765	12/1965	Rosenthal et al.	N/A	N/A
3420790	12/1968	Gassner et al.	N/A	N/A
3437621	12/1968	Aron et al.	N/A	N/A
3445275	12/1968	Bogart et al.	N/A	N/A
3449108	12/1968	McConnell et al.	N/A	N/A
3471303	12/1968	Hamdy et al.	N/A	N/A
3715024	12/1972	Mumma	N/A	N/A
3997674	12/1975	Ukai et al.	N/A	N/A
4002775	12/1976	Kabara	N/A	N/A
4002777	12/1976	Juvinall et al.	N/A	N/A
4025540	12/1976	Kleemann et al.	N/A	N/A
4115313	12/1977	Lyon et al.	N/A	N/A
4421775	12/1982	Chan, Jr.	N/A	N/A
4423071	12/1982	Chignac et al.	N/A	N/A
4505935	12/1984	Larsson	N/A	N/A
4649057	12/1986	Thomson	N/A	N/A
4654370	12/1986	Marriot et al.	N/A	N/A
4661359	12/1986	Seaborne et al.	N/A	N/A
4710228	12/1986	Seaborne et al.	N/A	N/A
4726898	12/1987	Mills et al.	N/A	N/A
4732708	12/1987	Ekman et al.	N/A	N/A
4820533	12/1988	Seaborne	N/A	N/A
4857345	12/1988	Sardo	N/A	N/A
4874618	12/1988	Seabor	N/A	N/A
4960600	12/1989	Kester et al.	N/A	N/A
4962885	12/1989	Coffee	N/A	N/A
5019403	12/1990	Krochta	N/A	N/A
5051448	12/1990	Shashoua	N/A	N/A

5110509	12/1991	Peter et al.	N/A	N/A
5126153	12/1991	Beck	N/A	N/A
5209410	12/1992	Wichmann et al.	N/A	N/A
5354573	12/1993	Gross et al.	N/A	N/A
5366995	12/1993	Savage	N/A	N/A
5376391	12/1993	Nisperos-Carriedo et al.	N/A	N/A
5389389	12/1994	Beck	N/A	N/A
5451266	12/1994	Kirk et al.	N/A	N/A
5498295	12/1995	Murch et al.	N/A	N/A
5543164	12/1995	Krochta et al.	N/A	N/A
5607970	12/1996	Ishihara	N/A	N/A
5658768	12/1996	Quinlan	N/A	N/A
5741505	12/1997	Beyer et al.	N/A	N/A
5827553	12/1997	Dimitroglou	N/A	N/A
5832527	12/1997	Kawaguchi	N/A	N/A
5906831	12/1998	Larsson et al.	N/A	N/A
5925395	12/1998	Chen	N/A	N/A
5939117	12/1998	Chen et al.	N/A	N/A
6010726	12/1999	Evans et al.	N/A	N/A
6033705	12/1999	Isaacs	N/A	N/A
6068867	12/1999	Nussinovitch	426/654	A23C 19/16
6136856	12/1999	Savage et al.	N/A	N/A
6162475	12/1999	Hagenmaier et al.	N/A	N/A
6165529	12/1999	Yang et al.	N/A	N/A
6241971	12/2000	Fox et al.	N/A	N/A
6254645	12/2000	Kellis et al.	N/A	N/A
6255451	12/2000	Koch et al.	N/A	N/A
6294186	12/2000	Beerse et al.	N/A	N/A
6348217	12/2001	Santos et al.	N/A	N/A
6503492	12/2002	McGlone et al.	N/A	N/A
6723364	12/2003	Bompeix et al.	N/A	N/A
6729552	12/2003	McEwen et al.	N/A	N/A
6783768	12/2003	Brown et al.	N/A	N/A
6822105	12/2003	Luxem	N/A	N/A
7247272	12/2006	Moerman et al.	N/A	N/A
7373135	12/2007	Najib-Fruchart et al.	N/A	N/A
7375135	12/2007	Naiib-Fruchart et al.	N/A	N/A
7550617	12/2008	Imig et al.	N/A	N/A
7588641	12/2008	Yogi et al.	N/A	N/A
7708822	12/2009	Lahav et al.	N/A	N/A
7732470	12/2009	Imig et al.	N/A	N/A
7754766	12/2009	Awad	N/A	N/A
7785897	12/2009	Agnes et al.	N/A	N/A
7851002	12/2009	Hekal et al.	N/A	N/A
7931926	12/2010	Lidster et al.	N/A	N/A
7943336	12/2010	Viksoe-Nielsen et al.	N/A	N/A
8101221	12/2011	Chen et al.	N/A	N/A
8119178	12/2011	Lidster et al.	N/A	N/A
8197870	12/2011	Krasutsky et al.	N/A	N/A
8247609	12/2011	Roques et al.	N/A	N/A
8263751	12/2011	Peterson	N/A	N/A
8424243	12/2012	Narciso et al.	N/A	N/A
8501445	12/2012	Yoshikawa et al.	N/A	N/A
8546115	12/2012	Buchert et al.	N/A	N/A
8586807	12/2012	Hatcher	N/A	N/A

8609169	12/2012	Chen et al.	N/A	N/A
8752328	12/2013	Kaiser et al.	N/A	N/A
8846355	12/2013	Yoshikawa et al.	N/A	N/A
8921351	12/2013	Perlman	N/A	N/A
9095152	12/2014	Munger	N/A	N/A
9102125	12/2014	Battersby et al.	N/A	N/A
9283173	12/2015	Lederman	N/A	N/A
9284432	12/2015	Yoshikawa et al.	N/A	N/A
9475643	12/2015	Odman et al.	N/A	N/A
9714399	12/2016	Verkuiil	N/A	N/A
9743670	12/2016	Grund	N/A	N/A
9743679	12/2016	Perez et al.	N/A	N/A
9744542	12/2016	Rogers	N/A	N/A
9770041	12/2016	Dong et al.	N/A	N/A
9957215	12/2017	Perez	N/A	N/A
10092014	12/2017	Holland et al.	N/A	N/A
10150132	12/2017	Hamamoto et al.	N/A	N/A
10239069	12/2018	Rogers	N/A	N/A
10266708	12/2018	Perez	N/A	N/A
10407377	12/2018	Balms	N/A	N/A
10517310	12/2018	Perez	N/A	N/A
10537115	12/2019	Holland et al.	N/A	N/A
10537130	12/2019	Rogers	N/A	N/A
10561155	12/2019	Bakus	N/A	N/A
11447646	12/2021	Perez et al.	N/A	N/A
11472970	12/2021	Perez et al.	N/A	N/A
11723377	12/2022	Holland et al.	N/A	N/A
2001/0026927	12/2000	Yokohama et al.	N/A	N/A
2001/0042341	12/2000	Hamersky et al.	N/A	N/A
2002/0043577	12/2001	Krasutsky et al.	N/A	N/A
2002/0123546	12/2001	Bigg et al.	N/A	N/A
2003/0044488	12/2002	Roskam	N/A	N/A
2003/0109727	12/2002	Krasutsky et al.	N/A	N/A
2003/0124228	12/2002	Goto	N/A	N/A
2003/0194445	12/2002	Kuhner et al.	N/A	N/A
2004/0022906	12/2003	Petacvich	N/A	N/A
2004/0071845	12/2003	Hekal	N/A	N/A
2004/0120919	12/2003	Nguyen et al.	N/A	N/A
2004/0220283	12/2003	Zhang et al.	N/A	N/A
2004/0241288	12/2003	Ahav et al.	N/A	N/A
2005/0053593	12/2004	Wang et al.	N/A	N/A
2005/0233039	12/2004	Wolfe et al.	N/A	N/A
2005/0249856	12/2004	Marangoni	N/A	N/A
2006/0037892	12/2005	Blanc	N/A	N/A
2006/0057187	12/2005	Eskuchen et al.	N/A	N/A
2006/0057259	12/2005	Ripoll et al.	N/A	N/A
2006/0153912	12/2005	Habich et al.	N/A	N/A
2006/0198924	12/2005	Song et al.	N/A	N/A
2006/0292281	12/2005	Kragh et al.	N/A	N/A
2007/0082094	12/2006	McClements et al.	N/A	N/A
2007/0278103	12/2006	Hoerr et al.	N/A	N/A
2008/0026120	12/2007	Petacvich	N/A	N/A
2008/0038471	12/2007	Boger et al.	N/A	N/A
2008/0119772	12/2007	Coffee	N/A	N/A
2008/0254987	12/2007	Liu et al.	N/A	N/A

2008/0262190	12/2007	Koskimies et al.	N/A	N/A
2008/0310991	12/2007	Webster et al.	N/A	N/A
2009/0035414	12/2008	Cheng et al.	N/A	N/A
2009/0042985	12/2008	Bhaggan et al.	N/A	N/A
2009/0104446	12/2008	Guillet et al.	N/A	N/A
2009/0123632	12/2008	Klemann et al.	N/A	N/A
2009/0142453	12/2008	Lobisser et al.	N/A	N/A
2009/0152371	12/2008	Stark et al.	N/A	N/A
2009/0163729	12/2008	Li et al.	N/A	N/A
2009/0224437	12/2008	Fukuoka et al.	N/A	N/A
2009/0325240	12/2008	Daniell	N/A	N/A
2010/0029778	12/2009	Bailey et al.	N/A	N/A
2010/0092631	12/2009	Sardo	N/A	N/A
2010/0104710	12/2009	Petcavich	N/A	N/A
2010/0186674	12/2009	Cahill, Jr. et al.	N/A	N/A
2010/0210745	12/2009	McDaniel	N/A	N/A
2010/0278784	12/2009	Pojasek et al.	N/A	N/A
2010/0292426	12/2009	Hossainv	N/A	N/A
2010/0297273	12/2009	Lederman	N/A	N/A
2011/0000975	12/2010	Gartstein et al.	N/A	N/A
2011/0003014	12/2010	Kulikowski	N/A	N/A
2011/0240064	12/2010	Wales	N/A	N/A
2011/0244095	12/2010	Sardo	N/A	N/A
2011/0280942	12/2010	Schad et al.	N/A	N/A
2012/0003356	12/2011	Ekanayake et al.	N/A	N/A
2012/0103790	12/2011	Krull et al.	N/A	N/A
2012/0251675	12/2011	Sowa et al.	N/A	N/A
2013/0045246	12/2012	Edwards et al.	N/A	N/A
2013/0095141	12/2012	Schad et al.	N/A	N/A
2013/0121648	12/2012	Hung et al.	N/A	N/A
2013/0156970	12/2012	Crawford	N/A	N/A
2013/0209617	12/2012	Lobisser et al.	N/A	N/A
2013/0216488	12/2012	Hernandez-Brenes et al.	N/A	N/A
2013/0280819	12/2012	Cooks et al.	N/A	N/A
2013/0323378	12/2012	Stark et al.	N/A	N/A
2014/0033926	12/2013	Passel et al.	N/A	N/A
2014/0199449	12/2013	Hernandez et al.	N/A	N/A
2014/0205722	12/2013	Quintanar Guerrero et al.	N/A	N/A
2014/0221308	12/2013	Baker et al.	N/A	N/A
2014/0234921	12/2013	Nyyssola et al.	N/A	N/A
2014/0348945	12/2013	Dong et al.	N/A	N/A
2014/0367478	12/2013	Roos et al.	N/A	N/A
2014/0377434	12/2013	Oguro et al.	N/A	N/A
2015/0021802	12/2014	Wakita	N/A	N/A
2015/0030780	12/2014	Rogers	N/A	N/A
2015/0079248	12/2014	Nussinovitch et al.	N/A	N/A
2015/0210855	12/2014	Firth	N/A	N/A
2015/0359217	12/2014	Narita et al.	N/A	N/A
2015/0366230	12/2014	Malefyt et al.	N/A	N/A
2016/0002483	12/2015	Zhao et al.	N/A	N/A
2016/0100597	12/2015	Immaraju et al.	N/A	N/A
2016/0213030	12/2015	Schad	N/A	N/A
2016/0256429	12/2015	Spanova et al.	N/A	N/A
2016/0304410	12/2015	Schultz et al.	N/A	N/A
2016/0324172	12/2015	Williams et al.	N/A	N/A

2017/0049119	12/2016	Perez et al.	N/A	N/A
2017/0073532	12/2016	Perez et al.	N/A	N/A
2017/0251673	12/2016	Cifuentes et al.	N/A	N/A
2017/0318827	12/2016	Perez et al.	N/A	N/A
2017/0320077	12/2016	Rogers	N/A	N/A
2017/0332650	12/2016	Holland	N/A	N/A
2018/0044276	12/2017	Perez et al.	N/A	N/A
2018/0092811	12/2017	Klee	N/A	N/A
2018/0179401	12/2017	Perez et al.	N/A	N/A
2018/0222835	12/2017	Bakus et al.	N/A	N/A
2018/0258296	12/2017	Perez et al.	N/A	N/A
2018/0303732	12/2017	Wehner et al.	N/A	N/A
2018/0317509	12/2017	Van Velzen et al.	N/A	N/A
2018/0368426	12/2017	Holland et al.	N/A	N/A
2018/0368427	12/2017	Rogers et al.	N/A	N/A
2019/0031590	12/2018	Bakus	N/A	N/A
2019/0104748	12/2018	Kaun et al.	N/A	N/A
2019/0166901	12/2018	Rogers	N/A	N/A
2019/0269144	12/2018	Kaun et al.	N/A	N/A
2019/0269145	12/2018	Bakus, II et al.	N/A	N/A
2019/0364916	12/2018	Jung et al.	N/A	N/A
2020/0068912	12/2019	Hernandez	N/A	N/A
2020/0085072	12/2019	Holland et al.	N/A	N/A
2020/0085092	12/2019	Rogers	N/A	N/A
2020/0093147	12/2019	Perez	N/A	N/A
2020/0100514	12/2019	Bakus	N/A	N/A
2020/0229455	12/2019	Perez	N/A	N/A
2020/0352184	12/2019	Frazier et al.	N/A	N/A
2020/0383343	12/2019	Rodriguez et al.	N/A	N/A
2021/0282432	12/2020	Hernandez et al.	N/A	N/A
2021/0337817	12/2020	Lee et al.	N/A	N/A
2021/0340354	12/2020	Wang et al.	N/A	N/A
2022/0039416	12/2021	Kaun et al.	N/A	N/A
2022/0064859	12/2021	Hernandez et al.	N/A	N/A
2022/0135510	12/2021	Bakus, II et al.	N/A	N/A
2022/0312784	12/2021	Chari et al.	N/A	N/A
2023/0072790	12/2022	Faust et al.	N/A	N/A
2023/0098477	12/2022	Perez et al.	N/A	N/A
2023/0232872	12/2022	Hernandez et al.	N/A	N/A
2023/0380435	12/2022	Holland et al.	N/A	N/A
2024/0008501	12/2023	Fisher et al.	N/A	N/A
2024/0090389	12/2023	Fisher et al.	N/A	N/A
2024/0130383	12/2023	Lin et al.	N/A	N/A
2024/0156117	12/2023	Crisci et al.	N/A	N/A
2024/0180180	12/2023	Essert et al.	N/A	N/A
2024/0180181	12/2023	Essert	N/A	N/A
2025/0024847	12/2024	Essert et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
86104531	12/1987	CN	N/A
1103548	12/1994	CN	N/A
1215420	12/1998	CN	N/A
1355806	12/2001	CN	N/A
1616561	12/2004	CN	N/A
1817147	12/2005	CN	N/A

1856261	12/2005	CN	N/A
1870912	12/2005	CN	N/A
101035926	12/2006	CN	N/A
101356012	12/2008	CN	N/A
101454406	12/2008	CN	N/A
101708013	12/2009	CN	N/A
101755899	12/2009	CN	N/A
102119719	12/2010	CN	N/A
102291986	12/2010	CN	N/A
102335142	12/2011	CN	N/A
102349555	12/2011	CN	N/A
103283830	12/2012	CN	N/A
103478233	12/2013	CN	N/A
103609670	12/2013	CN	N/A
103719261	12/2013	CN	N/A
103734280	12/2013	CN	N/A
104606076	12/2014	CN	N/A
104642528	12/2014	CN	N/A
105341619	12/2015	CN	N/A
105494615	12/2015	CN	N/A
106280909	12/2016	CN	N/A
107828560	12/2017	CN	N/A
107996698	12/2017	CN	N/A
110255947	12/2018	CN	N/A
112898630	12/2020	CN	N/A
113038824	12/2020	CN	N/A
2505428	12/1975	DE	N/A
3017221	12/1979	DE	N/A
3622191	12/1987	DE	N/A
102005043459	12/2006	DE	N/A
0104043	12/1983	EP	N/A
0253539	12/1987	EP	N/A
0655201	12/1994	EP	N/A
1020124	12/1999	EP	N/A
1681281	12/2005	EP	N/A
1721524	12/2005	EP	N/A
1854360	12/2006	EP	N/A
2389814	12/2010	EP	N/A
2644185	12/2012	EP	N/A
2684879	12/2013	EP	N/A
2889345	12/2014	EP	N/A
3354264	12/2017	EP	N/A
3673738	12/2019	EP	N/A
1041955	12/1998	ES	N/A
421649	12/1933	GB	N/A
192832	12/2003	IN	N/A
S54-139645	12/1978	JP	N/A
S58-034034	12/1982	JP	N/A
S58-89140	12/1982	JP	N/A
S62-126931	12/1986	JP	N/A
S63-062574	12/1987	JP	N/A
H04-016173	12/1991	JP	N/A
H04-507192	12/1991	JP	N/A
H06-506166	12/1993	JP	N/A
H07-075519	12/1994	JP	N/A

H08-056564	12/1995	JP	N/A
2519455	12/1995	JP	N/A
H10-298003	12/1997	JP	N/A
2002-531075	12/2001	JP	N/A
2003-522130	12/2002	JP	N/A
2004-526830	12/2003	JP	N/A
3835956	12/2005	JP	N/A
2007-502271	12/2006	JP	N/A
2007-510014	12/2006	JP	N/A
2008-504442	12/2007	JP	N/A
2009-527357	12/2008	JP	N/A
2010-530795	12/2009	JP	N/A
2012-087072	12/2011	JP	N/A
2012-515561	12/2011	JP	N/A
2013-139433	12/2012	JP	N/A
2014-231481	12/2013	JP	N/A
2018-529627	12/2017	JP	N/A
2018-534912	12/2017	JP	N/A
10-1419385	12/2013	KR	N/A
514588	12/1975	SU	N/A
1982/003173	12/1981	WO	N/A
93/06735	12/1992	WO	N/A
WO-0009138	12/1999	WO	A23J 7/00
2001/001980	12/2000	WO	N/A
2004/030455	12/2003	WO	N/A
2007/100654	12/2006	WO	N/A
2008/142393	12/2007	WO	N/A
2009/119730	12/2008	WO	N/A
2010/031929	12/2009	WO	N/A
2011/014831	12/2010	WO	N/A
2012/042404	12/2011	WO	N/A
2012/164561	12/2011	WO	N/A
2012/173262	12/2011	WO	N/A
2014/162238	12/2013	WO	N/A
2014/206911	12/2013	WO	N/A
2015/017450	12/2014	WO	N/A
2015/028299	12/2014	WO	N/A
2015/052433	12/2014	WO	N/A
2015/074144	12/2014	WO	N/A
2015/176020	12/2014	WO	N/A
2016/168319	12/2015	WO	N/A
2016/187581	12/2015	WO	N/A
2017/043972	12/2016	WO	N/A
2017/048951	12/2016	WO	N/A
2017/100636	12/2016	WO	N/A
2017/132281	12/2016	WO	N/A
2017/172951	12/2016	WO	N/A
2018/009846	12/2017	WO	N/A
2018/042435	12/2017	WO	N/A
2018/094269	12/2017	WO	N/A
WO 2018/144482	12/2017	WO	N/A
2019/058211	12/2018	WO	N/A
2019/096844	12/2018	WO	N/A
WO 2020/051238	12/2019	WO	N/A
WO 2020/247667	12/2019	WO	N/A

OTHER PUBLICATIONS

Scholfield et al. (In Journal of the American Oil Chemists Society vol. 58, No. 10, 889-892, 1981). (Year: 1981). cited by examiner

Lecithin [Retrieved on Jul. 30, 2023]. (Year: 2023). cited by examiner

Structure of phospholipids [Retrieved on Jul. 30, 2023]. (Year: 2023). cited by examiner

Phosphatidylcholine (Retrieved on 2023). (Year: 2023). cited by examiner

Wong et al. (See p. 3 of Science Direct : in Soybeans 2008). (Year: 2008). cited by examiner

Google search result (Retrieved on 2023). (Year: 2023). cited by examiner

Google search result for soy lecithin and phytosterol (Retrieved on Jul. 31, 2023). (Year: 2023). cited by examiner

Soy lecithin phytosterol (EFSA Journal / vol. 5, Issue 6 / 486: First published: Jun. 6, 2007
<https://doi.org/10.2903/j.efsa.2007.486>) (Year: 2007). cited by examiner

PCT International Search Report and Written Opinion in International Appln. No. PCT/US2021/044535, mailed Nov. 17, 2021, 16 pages. cited by applicant

PCT International Search Report and Written Opinion in International Appln. No. PCT/US2021/048301, mailed Dec. 7, 2021, 12 pages. cited by applicant

PCT International Search Report and Written Opinion in PCT/US18/46998, Dec. 27, 2018, 31 pages. cited by applicant

PCT International Search Report and Written Opinion in PCT/US2014/048707, Nov. 13, 2014, 14 pages. cited by applicant

PCT International Search Report and Written Opinion in PCT/US2017/024799, Jun. 8, 2017, 13 pages. cited by applicant

PCT International Search Report and Written Opinion in PCT/US2017/041167, Oct. 9, 2017, 16 pages. cited by applicant

PCT International Search Report and Written Opinion, PCT Application No. PCT/US16/33617, Aug. 26, 2016, 20 Pages. cited by applicant

PCT International Search Report and Written Opinion, PCT Application No. PCT/US17/62399, Feb. 16, 2018, 16 Pages. cited by applicant

PCT International Search Report and Written Opinion, PCT Application No. PCT/US2018/46994, Dec. 20, 2018, 28 pages. cited by applicant

PCT Invitation to Pay additional Fees and, Where Applicable, Protest Fee in International Appln. No. PCT/US2018/046994, mailed Oct. 23, 2018, 2 pages. cited by applicant

Perkins et al., "Ultrasonic fog application of organic acids delays postharvest decay in red bayberry," Postharvest Biology and Technology, Nov. 2017, 13:41-47. cited by applicant

Postharvest.ucdavis.edu [online], "Fact Sheets," available on or before Aug. 9, 2016, via Internet Archive: Wayback Machine URL
https://web.archive.org/web/20160809075048/http://postharvest.ucdavis.edu/Commodity_Resources/Fact_Sheets/>
 retrieved on Aug. 16, 2021, URL <http://postharvest.ucdavis.edu/Commodity_Resources/Fact_Sheets/>, 3 pages. cited by applicant

Quiros-Sauceda et al., "Edible coatings as encapsulating matrices for bioactive compounds: a review," Journal of Food Science and Technology, Jan. 2014, 51(9), pp. 1674-1685, 12 pages. cited by applicant

Rahman et al., "The Effect of a New Coating on the Drying Performance of Fruit and Vegetables Products: Experimental Investigation and Artificial Neural Network Modeling," Foods, Mar. 2020, 9(3), 308, 1-13. cited by applicant

Ramsay, "The Evaporation of Water from the Cockroach," Journal of Experimental Biology, Oct. 1935, 12 (4):373-383. cited by applicant

Roy, S. et al., "Modified atmosphere and modified humidity packaging of fresh mushrooms," J Food Sci., 1996, vol. 61, p. 391-397. cited by applicant

Rujun et al., "Surface Modification and Physical properties of Inorganic Nanomaterials," University of Technology Press, 1st Edition, Oct. 2009, 43-45, 11 pages (with English translation). cited by applicant

Rutala, W. et al., "Guideline for Disinfection and Sterilization in Healthcare Facilities, 2008," CDC, 2008, 158 Pages cited by applicant

Sasaki, M. et al., "Cellulose hydrolysis in subcritical and supercritical water," Journal of Supercritical Fluids, 1998, vol. 13, pp. 261-268. cited by applicant

Sasaki, M. et al., "Dissolution and Hydrolysis of Cellulose in Subcritical and Supercritical Water," Ind. Eng. Chem.

Res., 2000, vol. 39, pp. 2883-2890. cited by applicant

Savage, P., "Organic Chemical Reactions in Supercritical Water," Chem. Rev., 1999, vol. 99, pp. 603-621. cited by applicant

Schreiber et al., "Transport barriers made of cutin, suberin and associated waxes," Trends in Plant Science, 2010, vol. 15, No. 10, p. 546-553. cited by applicant

Schweizer, P. et al., "Perception of free cutin monomers by plant cells," The Plant Journal, vol. 10, No. 2, 1996, p. 331-341. cited by applicant

Schweizer, P. et al., "Plant Protection by Free Cutin Monomers in Two Cereal Pathosystems," Advances in Molecular Genetics of Plant-Microbe Interactions, 1994, p. 371-374. cited by applicant

Shirazi A, et al., "Controlling relative humidity in modified atmosphere packages of tomato fruit," HortScience, 1992, vol. 27, p. 336-339. cited by applicant

Siekmann et al., "Preparation and structural investigations of colloidal dispersions prepared from cubic monoglyceride-water phases," Int. J. Pharm., Sep. 2002, 244(1-2):33-43. cited by applicant

Spicer et al., "Novel Process for Producing Cubic Liquid Crystalline Nanoparticles (Cubosomes)," Langmuir, Aug. 2001, 17(19):5748-5756. cited by applicant

Steuter et al., "Water Potential of Aqueous Polyethylene Glycol," Plant Physiol., 1981, vol. 67, p. 64-67. cited by applicant

Storage and Preservation Techniques for Fruits and Vegetables, 1st ed., Scientific Research Achievements Management Office of the State Science and Technology Commission, Oct. 31, 1985, 40, 3 pages (with English translation). cited by applicant

Takats, Z., et al., "Special Feature: Perspective—Ambient Mass Spectrometry Using Desorption Electrospray Ionization (DESI): Instrumentation, Mechanisms and Applications in Forensics, Chemistry, and Biology," J. Mass Spectrom, 2005, vol. 40, pp. 1261-1275. cited by applicant

Tanaka, M., et al., "Quantitative determination of isomeric glycerides, free fatty acids and triglycerides by thin layer chromatography-flame ionization detector system." Lipids, 1980, vol. 15, No. 10, pp. 872-875. cited by applicant

Technical Evaluation Report, "Glycerides (mono and di) Handling/Processing," Compiled by OMRI for the USDA National Organic Program, Jan. 27, 2015, 1-14. cited by applicant

Tegelaar, E.W. et al., "Some mechanisms of flash pyrolysis of naturally occurring higher plant polyesters," Journal of Analytical and Applied Pyrolysis, 1989, vol. 15, 2 pages (abstract only). cited by applicant

The Fountainhead Group, Inc., "Burgess Electric Professional Fogger," Manual No. 161128, Revision D, Feb. 25, 2015, retrieved on Jan. 12, 2021, retrieved from URL <https://www.jondon.com/media/pdf/manuals/FG-EGF-EA_manual.pdf>, 8 pages. cited by applicant

Toro-Vazquez et al., "Physical properties of organogels and water in oil emulsions structured by mixtures of candelilla wax and monoglycerides," Food Research International, Oct. 2013, 54(2):1360-1368. cited by applicant

TW Search Report in Taiwan Appln. No. 105130215, dated Aug. 6, 2020, 12 pages (with English translation). cited by applicant

United States Environmental Protection Agency, "Containers and Packaging: Product-Specific Data," Nov. 6, 2019, last updated Jan. 28, 2021, retrieved on Oct. 6, 2021, retrieved from URL <<https://www.epa.gov/facts-and-figures-about-materials-waste-and-recycling/containers-and-packaging-product-specific-data>>, 12 pages. cited by applicant

US Statutory Invention Registration No. H1591, Preparation of Flavor-Enhanced Reduced Calorie Fried Foods, Sep. 3, 1996, 5 pages. cited by applicant

Van Doorn et al., "Alkylethoxylate surfactants for rehydration of roses and Bouvardia flowers," Postharvest Biology and Technology, 2002, vol. 24, p. 327-333. cited by applicant

Van Doorn et al., "Effects of surfactants on the longevity of dry-stored cut flowering stems of rose, Bouvardia, and Astilbe," Postharvest Biology and Technology, 1993, vol. 3, pp. 69-76. cited by applicant

Van Meeteren, "Water Relations and Keeping-Quality of Cut Gerbera Flowers. I. The Cause of Stem Break," Scientia Horticulturae, 1978, vol. 8, p. 65-74. cited by applicant

Vardar et al., "The application of various disinfectants by fogging for decreasing postharvest diseases of strawberry," Postharvest Biology and Technology, Apr. 2012, 66:30-34. cited by applicant

Vargas et al., "Development of Edible Coatings for Fresh Fruits and Vegetables: Possibilities and Limitations," Fresh Produce, Jan. 2008, 2(2):32-40. cited by applicant

Wang, R. et al., "Evolution of the Solvent Polarity in an Electrospray Plume," J. Am Soc Mass Spectrom, 2010, vol. 21, pp. 378-385. cited by applicant

Watkins, "The Use of 1-Methylcyclopropene (1-MCP) on Fruits and Vegetables," Biotech. Adv., Jul.-Aug. 2006, 24(4):389-409. cited by applicant

Weingartner, H. et al., "Supercritical water as a solvent," *Angewandte Chemie*, 2005, vol. 44, Issue 18, pp. 2672-2692. cited by applicant

Wikipedia, Anonymous, "Paint-Wikipedia," retrieved from URL <<https://en.wikipedia.org/w/index.php?title=Paint&oldid=563291624>>, retrieved Jul. 2013, 7 Pages. cited by applicant

Xizhong et al., "Spray drying," the 2nd edition, Chemical Industry Press, Feb. 28, 2003, 147-151, 9 pages. cited by applicant

Yang et al., "Progress on Graft Polymerization of Cellulose," *Journal of Cellulose Science and Technology*, Sep. 2009, 17(3), 6 pages (with English abstract). cited by applicant

Yeats, T. et al., "The identification of cutin synthase: formation of the plant polyester cutin," *Nat Chem Biol.*, Jul. 2012, vol. 8, No. 7, pp. 609-611, 10 pages. cited by applicant

Adkins et al., "Manipulating Avocado Fruit Ripening with 1-Methylcyclopropene," *Postharvest Biol. Technol.*, Jan. 2005, 35(1):33-42. cited by applicant

Alvaro, J. et al., "Effects of peracetic acid disinfectant on the postharvest of some fresh vegetables," *Journal of Food Engineering*, 2009, vol. 95, pp. 11-15. cited by applicant

Alvira et al., "Pretreatment Technologies for an Efficient Bioethanol Production Process Based on Enzymatic Hydrolysis: A Review," *Bio resource Technology*, 2010, 101(13):4851-4861. cited by applicant

Andrade, Ricardo D. et al., "Atomizing spray systems for application of edible coatings," *Comprehensive Reviews in Food Science and Food Safety*, vol. 11, No. 3, 2012, p. 323-337. cited by applicant

Angelico et al., "Phase Diagram and Phase Properties of the System Lecithin-Water-Cyclohexane," *Langmuir*, 2000, 16(5):2124-2132. cited by applicant

Ayala-Zavala, J.F. et al., "High Relative Humidity In-Package of Fresh-Cut Fruits and Vegetables: Advantage or Disadvantage Considering Microbiological Problems and Antimicrobial Delivering Systems?," *J Food Science*, 2008, vol. 73, p. R41-R47. cited by applicant

Baker et al., "Cutin Degradation by Plant Pathogenic Fungi," *The American Phytopathological Society*, May 15, 1978, 68:1577-1584. cited by applicant

Baldwin et al., "Edible Coatings for Lightly Processed Fruits and Vegetables," *HortScience*, Feb. 1995, 30(1):35-38. cited by applicant

Banerjee, S. et al., "Review Article: Electrospray Ionization Mass Spectrometry: A Technique to Access the Information Beyond the Molecular Weight of the Analyte," *International Journal of Analytical Chemistry*, Nov. 2011, vol. 2012, Article ID 282574, 40 pages. cited by applicant

Bateman, A. et al., "The Effect of Solvent on the Analysis of Secondary Organic Aerosol Using Electrospray Ionization Mass Spectrometry," *Environ. Sci. Technol.*, 2008, vol. 42, No. 19, pp. 7341-7346. cited by applicant

Bateman, A., et al., "Supporting Information for Manuscript es-2008-01226w—The Effect of Solvent on the Analysis of Secondary Organic Aerosol Using Electrospray Ionization Mass Spectrometry," [online] 2008; available from the Internet URL: <http://aerosol.chem.uci.edu/publications/Irvine/2008.sub.-Bateman.sub.-EST.sub.--SOA.sub.-solvent.sub.-effects.sub.--supporting.sub.-info.pdf>, 6 pages. cited by applicant

Bell et al., "The activity of (S)-hydroprene space spray against three stored products pests in a simulated food production environment," *Journal of Stored Products Research*, Apr. 1999, 35(2):117-126. cited by applicant

Ben-Yehoshua, S. et al., "Modified-atmosphere packaging of fruits and vegetables: reducing condensation of water in bell peppers and mangoes," *Acta Hort (ISHS)*, 1998, vol. 464, 387-392. cited by applicant

Berge et al., "Pharmaceutical Salts," *J. Pharm. Sci.*, Jan. 1977, 66(1):1-19. cited by applicant

Bewick, T. et al., "Evaluation of Epicuticular Wax Removal from Whole Leaves with Chloroform," *Weed Technology*, Jul. 1993, vol. 7, No. 3, pp. 706-716. cited by applicant

Bourtoom, T., "Edible films and coatings: characteristics and properties," *International Food Research Journal*, 2008, vol. 15, No. 3, pp. 237-248, 13 pages. cited by applicant

Brunk et al., "HyphaTracker: An ImageJ toolbox for time-resolved analysis of spore germination in filamentous fungi," *Scientific Reports*, Jan. 2018, 8(605):1-13. cited by applicant

Cantwell, M., "Properties and recommended conditions for long-term storage of fresh fruits and vegetables," Nov. 2001, 8 Pages. cited by applicant

Cech, N., et al., "Practical Implications of Some Recent Studies in Electrospray Ionization Fundamentals," *Mass Spectrometry Reviews*, 2001, vol. 20, pp. 362-387. cited by applicant

Chen, D-R., et al., "Electrospraying of Conducting Liquids for Monodisperse Aerosol Generation in the 4 nm to 1.8. mu.m Diameter Range," *J. Aerosol Sci.*, 1995, vol. 26, No. 6, pp. 963-977. cited by applicant

Cochran, H.D., "Solvation in supercritical water," *Fluid Phase Equilibria*, 1992, vol. 71, pp. 1-16. cited by applicant

Cook et al., "The use of trifluoroacetic anhydride in the synthesis of glycerides," *Journal of Chemical Society*, 1965,

4594-4596. cited by applicant

Dao et al., "Control of Food Spoilage Fungi by Ethanol," Food Control, Mar. 2011, 22(3-4):360-368. cited by applicant

D'Aquino et al., "Postharvest Lecithin Application Improves Storability of 'Primosole' Pomegranates," Acta Horticulturae, Jun. 2012, 934:733-739. cited by applicant

Deell JR et al., "Addition of sorbitol with KMnO₄ improves broccoli quality retention in modified atmosphere packages," J Food Qual, 2006, vol. 29, p. 65-75. cited by applicant

Dhall, "Advances in edible coatings for fresh fruits and vegetables: a review," Crit. Rev. Food Sci. Nutr., 2013, 53(5) pp. 435-450. cited by applicant

Dinani et al., "Optimization of Carboxymethyl Cellulose and Calcium Chloride Dip-Coating on Mushroom Slices Prior to Hot Air Drying Using Response Surface Methodology," Journal of Food Processing and Prevention, Jun. 2014, 38(3):1269-1278. cited by applicant

Duoren et al., "Green Plasticizers," Scientific and Technological Literature Publishing House, the 1st Edition, Oct. 2011, 339-340, 7 pages (with English translation). cited by applicant

Elgimabi and Ahmed, "Effects of Bactericides and Sucrose-Pulsing on Vase Life of Rose Cut Flowers (*Rosa hybrida*)," Botany Research International, 2009, 2(3) p. 164-168. cited by applicant

Enke, C., "A Predictive Model for Matrix and Analyte Effects in Electrospray Ionization of Singly-charged Ionic Analytes," Analytical Chemistry, 1997, vol. 69, No. 23, pp. 4885-4893. cited by applicant

Extended European Search Report for European Patent Application No. EP 14831592.2, Mar. 2, 2017, 9 Pages. cited by applicant

Extended European Search Report in European Patent Appln. No. EP 19857630.8, dated May 20, 2022, 9 pages. cited by applicant

Gabler, M., et al., "Impact of Postharvest Hot Water or Ethanol Treatment of Table Grapes on Gray Mold Incidence, Quality, and Ethanol Content," Plant Disease, Mar. 2005, vol. 89, No. 3, pp. 309-316. cited by applicant

Gaskell, S., "Special Feature: Tutorial—Electrospray: Principles and Practice," J. Mass Spectrom, 1997, vol. 32, pp. 677-688. cited by applicant

Gibbs, "Water-Proofing Properties of Cuticular Lipids," American Zoologist, Jun. 1998, 38(3):471-482. cited by applicant

Gil, M. et al., "Fresh-cut product sanitation and wash water disinfection: Problems and solutions," International Journal of Food Microbiology, 2009, vol. 134, pp. 37-45. cited by applicant

Graca, "Suberin: the biopolyester at the frontier of plants," Frontiers in Chemistry, Oct. 2015, 3(62):1-11. cited by applicant

Graca, J. et al., "Glycerol and glyceryl esters of o-hydroxyacids in cutins," Phytochemistry, 2002, vol. 61, pp. 205-215. cited by applicant

Graca, J. et al., "Linear and branched poly (omega-hydroxyacid) esters in plant cutins," J. Agric. Food Chem., 2010, vol. 58, No. 17, pp. 9666-9674. cited by applicant

Hardenburg, R., et al., "The Commercial Storage of Fruits, Vegetables, and Florist and Nursery Stocks," United States Department of Agriculture, Agriculture Handbook No. 66, Sep. 1986, pp. 6-7, 30, 50-51. cited by applicant

Hauff, S. et al., "Determination of hydroxylated fatty acids from the biopolymer of tomato cutin and their fate during incubation in soil," Phytochemical Analysis, Aug. 26, 2010, vol. 21, No. 6, pp. 582-589. cited by applicant

He et al., "Stem end blockage in cut Grevillea 'Crimson Yul-lo' inflorescences," Postharvest Biology and Technology, 2006, vol. 41, p. 78-84. cited by applicant

Herrero et al., "Compressed fluids for the extraction of bioactive compounds," TrAC Trends in Analytical Chemistry, 2013, 43(1):67-83. cited by applicant

Hoa et al., "Effects of different coatings on biochemical changes of 'cat Hoa loc' mangoes in storage," Postharvest Biology and Technology, Nov. 2007, 48(1):150-152. cited by applicant

Hofmann et al., "The behavior and solubility of monoglycerides in dilute, micellar bile-salt solution," BBA—Specialised Section on Lipids and Related Subjects, Jan. 1963, 70:306-316. cited by applicant

Hojjati et al., "Chemical Treatments of Eustoma Cut Flower Cultivars for Enhanced Vase Life," Journal of Agriculture and Social Sciences, 2007, vol. 3, No. 3, p. 75-78. cited by applicant

Holcroft, D., "Water Relations in Harvested Fresh Produce," PEF White Paper No. 15-01, The Postharvest Education Foundation (PEF), May 2015, 16 Pages. cited by applicant

Hongyou, "Homemade Fruit and Vegetable Coating Preservative," Vegetables, Nov. 30, 2005, p. 39, 2 pages (with English translation). cited by applicant

Hoover et al., "The Effect of Monoglycerides on Amylose Complexing During a Potato Granule Process," Starch-Sta

RKE, Oct. 1981, 33(10):346-355. cited by applicant

Huang et al., "Automation of a Fourier transform ion cyclotron resonance mass spectrometer for acquisition, analysis, and e-mailing of high-resolution exact-mass electrospray ionization mass spectral data," Journal of the American Society for Mass Spectrometry, Nov. 1, 1999, 10(11):1166-1173. cited by applicant

Huang, T-Y., et al., "Electron Transfer Reagent Anion Formation via Electrospray Ionization and Collision-induced Dissociation," Anal Chem., 2006, vol. 78, No. 21, pp. 7387-7391, 9 pages. cited by applicant

Hudson, B., "Fatty Acids," Encyclopedia of Food Sciences and Nutrition (Second Edition), 2003, pp. 2297-2300. cited by applicant

International Search Report and Written Opinion in International Appln. No. PCT/US2021/057448, mailed Feb. 18, 2022, 17 pages. cited by applicant

International Search Report and Written Opinion in International Appln. No. PCT/US2022/042924, mailed Dec. 9, 2022, 18 pages. cited by applicant

International Search Report and Written Opinion in International Appln. No. PCT/US2022/043079, mailed Dec. 6, 2022, 15 pages. cited by applicant

Javad et al., "Effect of Cultivar on Water Relations and Postharvest Quality of Gerbera (*Gerbera jamesonii* Bolus ex. Hook f.) Cut Flower," World Applied Sciences Journal, 2012, vol. 18, No. 5, p. 698-703. cited by applicant

Javad et al., "Postharvest evaluation of vase life, stem bending and screening of cultivars of cut gerbera (*Gerbera jamesonii* Bolus ex. Hook f.) flowers," African Journal of Biotechnology 2011, 10(4), p. 560-566. cited by applicant

Jaworek, A., "Electrospray Droplet Sources for Thin Film Deposition," J. Mater Sci, 2007, vol. 42, pp. 266-297. cited by applicant

Jenkins, S. et al., "Isolation and Compositional Analysis of Plant Cuticle Lipid Polyester Monomers," Journal of Visualized Experiments, 105 e53386, 10 pages, URL: <https://www.jove.com/video/53386>. cited by applicant

Jensen et al., "Estimation of the Monoglyceride Content of Milk," Journal of Dairy Science, 1959, 42(2):232-239. cited by applicant

Jerome, F., et al., "One pot" and selective synthesis of monoglycerides over homogeneous and heterogeneous guanidine catalysts," Green Chem., 2004, vol. 6, pp. 72-74. cited by applicant

Jiabin, "Rubberized fabrics and products thereof," World Rubber Industry, Dec. 2000, 6:27-32, 24 pages (with English translation). cited by applicant

Jingmei et al., "Preparation of modified starch/polylactic acid blends," New Chemical Materials, Jun. 2011, 39(6):125-126 and 129 (with English abstract). cited by applicant

Jones et al., "Pulsing with Triton X-100 Improves Hydration and Vase Life of Cut Sunflowers (*Helianthus annuus* L.)," HortScience, 1993, vol. 28, No. 12, p. 1178-1179. cited by applicant

Karabulut, O. et al., "Postharvest ethanol and hot water treatments of table grapes to control gray mold," Postharvest Biology and Technology, 2004, vol. 34, pp. 169-177. cited by applicant

Kebarle, P., "Special Feature: Commentary—A Brief Overview of the Present Status of the Mechanisms Involved in Electrospray Mass Spectrometry," J. Mass Spectrom, 2000, vol. 35, pp. 804-817. cited by applicant

Keller, B., et al., "Review Article: Interferences and Contaminants Encountered in Modern Mass Spectrometry," Analytica Chimica Acta, 2008, vol. 627, pp. 71-81. cited by applicant

Khan et al., "Application of Edible Coating for Improving Meat Quality: A Review," Pakistan Journal of Food Sciences, 2013, 23(2):71-79. cited by applicant

Kolattukudy, P.E., "Biopolyester Membranes of Plants: Cutin and Suberin," Science, 1980, vol. 208, No. 4447, pp. 990-1000. cited by applicant

Kolattukudy, P.E., "Cutin from plants," Biopolymers Online, 3a, 2005, 40 pages. cited by applicant

Krammer, P., et al., "Hydrolysis of esters in subcritical and supercritical water," Journal of Supercritical Fluids, 2000, vol. 16, pp. 189-206. cited by applicant

Krog et al., "Phase behaviour and rheological properties of aqueous systems of industrial distilled monoglycerides," Chemistry and Physics of Lipids, Feb. 1968, 2(1):129-143. cited by applicant

Kroll, B., et al., "Review: Chemistry of Secondary Organic Aerosol: Formation and Evolution of Low-volatility Organics in the Atmosphere," Atmospheric Environment, 2008, vol. 42, pp. 3593-3624. cited by applicant

Kubo et al., "Modes of antifungal action of alkanols against *Saccharomyces cerevisiae*," Bioorganic & Medicinal Chemistry, Mar. 2003, 11(6):1117-1122. cited by applicant

Kubo et al., "Structural functions of antimicrobial long-chain alcohols and phenols," Bioorganic & Medicinal Chemistry, Jul. 1995, 3(7):873-880. cited by applicant

Kulkarni et al., "Natural Polymers—A comprehensive review," International Journal of Research in Pharmaceutical

and Biomedical Sciences, Dec. 2012, 3(4):1597-1613. cited by applicant

kumitasu.com [online], "About fruit wax and chenpi," Jul. 26, 2015, retrieved on Aug. 16, 2021, retrieved from URL <<https://web.archive.org/web/20160409110129/https://www.kumitasu.com/contents/hyoji/806>>, 5 pages (with machine translation). cited by applicant

Li, M., et al., "Direct Quantification of Organic Acids in Aerosols by Desorption Electrospray Ionization Mass Spectrometry," *Atmospheric Environment*, 2009, vol. 43, pp. 2717-2720. cited by applicant

Lin et al., "Innovations in the Development and Application of Edible Coatings for Fresh and Minimally Processed Fruits and Vegetables," *Compr. Rev. Food Sci. Food Saf.*, Jun. 2007, 6(3):60-75. cited by applicant

Loppinet-Serani, A et al., "Supercritical water for environmental technologies," *J Chem Technol Biotechnol*, Jan. 12, 2010, vol. 85, pp. 583-589. cited by applicant

Martin, "Preparation of Saturated and Unsaturated Symmetrical Monoglycerides," *Journal of American Chemical Society*, Jun. 1953, 75(20):5482-5483. cited by applicant

Matic, M., "The chemistry of Plant Cuticles: a study of cutin form *Agave americana* L.," *Biochemical Journal*, 1956, vol. 63, No. 1, pp. 168-176. cited by applicant

Mattson, F.H., et al., "Synthesis and properties of glycerides," *J Lipid Research*, Jul. 1962, vol. 3, No. 3, pp. 281-296. cited by applicant

Meihu et al., "Research on Coating of Preserved Egg for Quality-keeping and Fresh-keeping," *Wan Fang*, Aug. 2007, 17 pages (with English translation). cited by applicant

Morton, H., "The Relationship of Concentration and Germicidal Efficiency of Ethyl Alcohol," *Annals New York Academy of Sciences*, 53(1), 1950, pp. 191-196. cited by applicant

Mukherjee et al., "Antibacterial activity of long-chain fatty alcohols against mycobacteria," *FEMS Microbiol. Lett.*, Jan. 2013, 338(2):177-183. cited by applicant

Nemoto et al., "Polyols of a cascade type as a water-solubilizing element of carborane derivatives for boron neutron capture therapy," *The Journal of Organic Chemistry*, Jan. 1992, 57(2):435. cited by applicant

Nizkorodov, S. et al., "Molecular Chemistry of Organic Aerosols through the Application of High Resolution Mass Spectrometry," *Phys. Chem. Chem. Phys*, 2011, vol. 13, pp. 3612-3629. cited by applicant

Oh, D. et al., "Antimicrobial activity of ethanol, glycerol monolaurate or lactic acid against *Listeria monocytogenes*," *International Journal of Food Microbiology*, 1993, vol. 20, pp. 239-246. cited by applicant

Olmez, H. et al., "Potential alternative disinfection methods for organic fresh-cut industry for minimizing water consumption and environmental impact," *LWT—Food Science and Technology*, 2009, vol. 42, pp. 686-693. cited by applicant

Orts et al., "Edible Films and Coatings: Why, What, and How?," *Edible Films and Coatings for Food Applications*, 2009, Chapter 1:1-23. cited by applicant

Osman, S. F. et al., "Preparation, Isolation, and Characterization of Cutin Monomers and oligomers from Tomato Peels," *J. Agric. Food Chem*, 1999, vol. 47, No. 2, pp. 799-802. cited by applicant

PCT International Search Report and Written Opinion for PCT/US2016/051936, Jan. 31, 2017, 18 Pages. cited by applicant

PCT International Search Report and Written Opinion for PCT/US2016/065917, Mar. 9, 2017, 10 Pages. cited by applicant

PCT International Search Report and Written Opinion for PCT/US2017/014978, Apr. 10, 2017, 13 Pages. cited by applicant

PCT International Search Report and Written Opinion in International Appln. No. PCT/US2019/042693, dated Oct. 2, 2019, 8 pages. cited by applicant

PCT International Search Report and Written Opinion in International Appln. No. PCT/US2019/045784, mailed Oct. 22, 2019, 14 pages. cited by applicant

PCT International Search Report and Written Opinion in International Appln. No. PCT/US2019/049585, mailed Jan. 13, 2020, 14 pages. cited by applicant

PCT International Search Report and Written Opinion in International Appln. No. PCT/US2020/036174, dated Sep. 7, 2020, 32 pages. cited by applicant

PCT International Search Report and Written Opinion in International Appln. No. PCT/US2021/020692, mailed Jun. 1, 2021, 13 pages. cited by applicant

Zhu, J. et al., "Focus: Electrospray—Formation and Decompositions of Chloride Adduct Ions, [M + Cl]⁻, in Negative Ion Electrospray Ionization Mass Spectrometry," *J. Am Soc Mass Spectrom*, 2000, vol. 11, pp. 932-941. cited by applicant

Zhu, J. et al., "Ranking of a Gas-phase Acidities and Chloride Affinities of Monosaccharides and Linkage Specificity

in Collision-induced Decompositions of Negative Ion Electrospray-generated Chloride Adducts of Oligosaccharides,” J. Am Soc Mass Spectrom, 2001, vol. 12, pp. 1193-1204. cited by applicant

Baldwin et al., “Use of Lipids in Coatings for Food Products,” Food Technology, Jun. 1997, 51(6): 56-61, 8 pages. cited by applicant

Czajka et al., “Surfactants at the Design Limit,” Langmuir, Mar. 2015, 31(30):8205-8217. cited by applicant

Mulqueen et al., “Prediction of Equilibrium Surface Tension and Surface Adsorption of Aqueous Surfactant Mixtures Containing Zwitterionic Surfactants,” Langmuir, Sep. 2000, 16(20):7640-7654. cited by applicant

wikipedia.org [online], “Coffee ring effect,” retrieved from URL <https://en.wikipedia.org/wiki/Coffee_ring_effect>, retrieved Dec. 29, 2023, 6 pages. cited by applicant

CAS No. 1286686-34-7, “Sunflower Wax,” Koster Keunen, retrieved on Feb. 5, 2024, retrieved from URL <<https://www.kosterkeunen.com/waxes/sunflower-wax/>>, 3 pages. cited by applicant

CAS No. 8006-40-4, “BEESWAX,” Chemical Book, retrieved on Feb. 5, 2024, retrieved from URL <https://www.chemicalbook.com/CASEN_8006-40-4.htm>, 3 pages. cited by applicant

CAS No. 8006-44-8, “Candelilla wax,” Sigma-Aldrich, retrieved on Feb. 5, 2024, retrieved from URL <<https://www.sigmaaldrich.com/US/en/product/aldrich/432288>>, 4 pages. cited by applicant

CAS No. 8012-89-3, “Bee's Wax,” Chemical Book, retrieved on Feb. 5, 2024, retrieved from URL <https://www.chemicalbook.com/ProductChemicalPropertiesCB9684201_EN.htm>, 3 pages. cited by applicant

CAS No. 8015-86-9, “Carnauba Wax,” Sigma-Aldrich, retrieved on Feb. 5, 2024, retrieved from URL <<https://www.sigmaaldrich.com/US/en/product/usp/1096860>>, 4 pages. cited by applicant

community JMP.com [online], “Designing Mixture Experiments—Part 1,” Sep. 19, 2022, retrieved on Feb. 5, 2024, retrieved from URL <https://community.jmp.com/t5/Mastering-JMP/Designing-Mixture-Experiments-Part-1/ta-p/546086/redirect_from_archived_page/true>, 7 pages. cited by applicant

Desai et al., “Melt granulation: An alternative to traditional granulation techniques,” Indian Drugs, Mar. 2013, 50(3):5-13, 10 pages. cited by applicant

International Search Report and Written Opinion in International Appln. No. PCT/US2023/033480, mailed Feb. 1, 2024, 18 pages. cited by applicant

Shanmugam, “Granulation techniques and technologies: recent progresses,” BioImpacts, Feb. 2015, 5(1):55-63. cited by applicant

Bourlieu-Lacanal et al., “Edible Moisture Barriers: Materials, Shaping Techniques and Promises in Food Product Stabilization,” Food Materials Science: Principles and Practice, Jan. 2007, retrieved from URL <<https://hal.archives-ouvertes.fr/hal-01454497/document>>, 38 pages. cited by applicant

Kester et al., “Edible Films and Coatings: A Review Further Research is Needed for Edible Films and Coatings to Help Sustain Product Freshness and Microbial Stability,” Food Technology, Dec. 1986, 40(12):47-59. cited by applicant

Primary Examiner: Kashnikow; Erik

Assistant Examiner: Mukhopadhyay; Bhaskar

Attorney, Agent or Firm: Fish & Richardson P.C.

Background/Summary

CROSS REFERENCE TO RELATED APPLICATION (1) This application claims priority to U.S. Provisional Application Ser. No. 63/241,991, filed on Sep. 8, 2021, the disclosure of which is incorporated by reference in its entirety.

TECHNICAL FIELD

(1) This invention relates to protective coatings for agricultural products and methods of application and use thereof.

BACKGROUND

(2) Common agricultural products are susceptible to degradation and decomposition (e.g., spoilage) when exposed to the environment. Such agricultural products can include, for example, eggs, fruits, vegetables, produce, seeds, nuts, flowers, and/or whole plants (including their processed and semi-processed forms). Edible non-agricultural products (e.g., vitamins, candy, etc.) can also be vulnerable to degradation when

exposed to the ambient environment. The degradation of agricultural and other edible products can occur via abiotic means as a result of evaporative moisture loss from an external surface of the products to the atmosphere, oxidation by oxygen that diffuses into the products from the environment, mechanical damage to the surface, and/or light-induced degradation (e.g., photodegradation). Biotic stressors such as bacteria, fungi, viruses, and/or pests can also infest and decompose the products.

(3) The cells that form the aerial surface of most plants (such as higher plants) include an outer envelope or cuticle, which provides varying degrees of protection against water loss, oxidation, mechanical damage, photodegradation, and/or biotic stressors, depending upon the plant species and the plant organ (e.g., fruit, seeds, bark, flowers, leaves, stems, etc.). Cutin, which is a biopolyester derived from cellular lipids, forms the major structural component of the cuticle and serves to provide protection to the plant against environmental stressors (both abiotic and biotic). The thickness, density, as well as the composition of the cutin (i.e., the different types of monomers that form the cutin and their relative proportions) can vary by plant species, by plant organ within the same or different plant species, and by stage of plant maturity. The cutin-containing portion of the plant can also contain additional compounds (e.g., epicuticular waxes, phenolics, antioxidants, colored compounds, proteins, polysaccharides, etc.). This variation in the cutin composition as well as the thickness and density of the cutin layer between plant species, plant organs and/or a given plant at different stages of maturation can lead to varying degrees of resistance between plant species or plant organs to attack by environmental stressors (i.e., water loss, oxidation, mechanical injury, and light) and/or biotic stressors (e.g., fungi, bacteria, viruses, insects, etc.).

(4) Conventional approaches to preventing degradation, maintaining quality, and increasing the life of agricultural products include special packaging and/or refrigeration. Refrigeration requires capital-intensive equipment, demands constant energy expenditure, can cause damage or quality loss to the product if not carefully controlled, must be actively managed, and its benefits are lost upon interruption of a temperature-controlled supply chain. Produce mass loss (e.g., water loss) during storage increases humidity, which necessitates careful maintenance of relative humidity levels (e.g., using condensers) to avoid negative impacts (e.g., condensation, microbial proliferation, etc.) during storage. Moreover, respiration of agricultural products is an exothermic process which releases heat into the surrounding atmosphere. During transit and storage in shipping containers, heat generated by the respiration of the agricultural product, as well as external environmental conditions and heat generated from mechanical processes (e.g., motors) necessitates active cooling of the storage container in order to maintain the appropriate temperature for storage, which is a major cost driver for shipping companies. By reducing the rate of degradation, reducing the heat generation in storage and transit, and increasing the shelf life of agricultural products, there is a direct value to the key stakeholders throughout the supply chain.

(5) There exists a need for new, more cost-effective approaches to prevent degradation, reduce the generation of heat and humidity, maintain quality, and increase the life of agricultural products. Such approaches may require less or no refrigeration, special packaging, etc.

SUMMARY

(6) Compositions and formulations for forming protective coatings and methods of making and using the coatings thereof are described herein. The components of the coatings form glycerophospholipid bilayer structures on the surface of the substrate (e.g., agricultural product) the coatings are disposed on, thus forming a protective barrier. In some embodiments, the protective barrier exhibits a low water and gas permeability. For example, the lattice formation that the molecules of the lamella adopt and the intermolecular forces between the lamellae can reduce loss of water or gas from the substrate. In some embodiments, the water and gas permeability of the coatings described herein can be modified by, e.g., (1) changing the components or amounts of the components in the composition (e.g., coating agent) applied to the substrate, as well as (2) modifying the method used to form the coating (e.g., the temperature or speed at which the mixture comprising the coating agent on the substrate is dried and/or the concentration of the coating agent in the mixture applied to the substrate). In some embodiments, the coating agents and/or coatings formed comprise a glycerophospholipid. In some embodiments, the coatings described herein are a more effective barrier to water and gas than, e.g., conventional wax coatings. In some such embodiments, the thickness of the coating is less than the thickness of conventional wax coatings.

(7) A method of reducing the ripening rate of an agricultural product is also described herein. The method comprises applying a solution comprising a glycerophospholipid to a surface of the agricultural product and drying the solution on the surface of the agricultural product under a forced flow of air to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby

forming a glycerophospholipid layer on the agricultural product.

(8) Although the disclosed inventive concepts include those defined in the attached claims, it should be understood that the inventive concepts can also be defined in accordance with the following embodiments.

(9) In addition to the embodiments of the attached claims and the embodiments described above, the following numbered embodiments are also innovative.

(10) Embodiment 1 is a method of reducing the ripening rate of an agricultural product, the method comprising: applying a solution comprising one or more glycerophospholipids to a surface of the agricultural product, wherein a temperature of the solution is between about 10° C. and about 80° C.; and drying the solution on the surface of the agricultural product under a flow of air having a temperature between about 20° C. and about 100° C. to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a glycerophospholipid layer on the agricultural product.

(11) Embodiment 2 is the method of embodiment 1, wherein the one or more glycerophospholipids comprise one or more of phosphatidylcholine, phosphatidylethanolamine, phosphatidylinositol, phosphatidylserine, and phosphatidic acid.

(12) Embodiment 3 is the method of embodiment 1 or embodiment 2, wherein the one or more glycerophospholipids comprise one or more compounds of Formula I:

(13) ##STR00001##

wherein: R.sup.1 is —H or one of the following fragments:

(14) ##STR00002##

and R.sup.2 and R.sup.3 are each independently, at each occurrence, —H or a fragment represented by Formula II:

(15) ##STR00003##

wherein: R.sup.4, R.sup.5, R.sup.8, R.sup.9, R.sup.12, R.sup.13, R.sup.14, R.sup.15 and R.sup.16 are each independently, at each occurrence, —H, —OH, —OR.sup.17 or C.sub.1-C.sub.6 alkyl; R.sup.6, R.sup.7, R.sup.10, and R.sup.11 are each independently, at each occurrence, —H, —OR.sup.17, or C.sub.1-C.sub.6 alkyl; and/or R.sup.4 and R.sup.5 can combine with the carbon atoms to which they are attached to form C=O; and/or R.sup.8 and R.sup.9 can combine with the carbon atoms to which they are attached to form C=O; and/or R.sup.12 and R.sup.13 can combine with the carbon atoms to which they are attached to form C=O; and R.sup.17 is at each occurrence C.sub.1-C.sub.6 alkyl, the symbol  custom character represents a single bond or a cis or trans double bond; n is 0, 1, 2, 3, 4, 5, 6, 7 or 8; m is 0, 1, 2 or 3; q is 0, 1, 2, 3, 4 or 5; and r is 0, 1, 2, 3, 4, 5, 6, 7 or 8.

(16) Embodiment 4 is the method of embodiment 3, wherein the fragment represented by Formula II is one of:

(17) ##STR00004## ##STR00005## ##STR00006## ##STR00007##

(18) Embodiment 5 is the method of any one of embodiments 1-4, wherein the one or more glycerophospholipids comprise phosphatidylcholine, phosphatidylethanolamine, and phosphatidylinositol.

(19) Embodiment 6 is the method of embodiment 5, wherein the one or more glycerophospholipids comprise about 20 wt % to about 40 wt % phosphatidylcholine, about 20 wt % to about 40 wt % phosphatidylethanolamine, and about 20 wt % to about 40 wt % phosphatidylinositol.

(20) Embodiment 7 is the method of embodiment 5 or embodiment 6, wherein the one or more glycerophospholipids further comprise phosphatidylserine.

(21) Embodiment 8 is the method of embodiment 7, wherein the one or more glycerophospholipids comprise less than about 5 wt % phosphatidylserine.

(22) Embodiment 9 is the method of any one of embodiments 1-8, wherein the solution further comprises a phytosterol.

(23) Embodiment 10 is the method of embodiment 9, wherein a weight ratio of the phytosterol to a total amount of the glycerophospholipids is less than about 0.05.

(24) Embodiment 11 is the method of any one of embodiments 1-10, wherein a total concentration of the one or more glycerophospholipids in the solution is between about 10 g/L and about 200 g/L.

(25) Embodiment 12 is the method of any one of embodiments 1-11, wherein a total concentration of the one or more glycerophospholipids in the solution is between about 50 g/L and about 150 g/L.

(26) Embodiment 13 is the method of any one of embodiments 1-10, wherein a total concentration of the one or more glycerophospholipids in the solution is between about 80 g/L and about 120 g/L.

(27) Embodiment 14 is the method of any one of embodiments 1-10, wherein a total concentration of the one or more glycerophospholipids in the solution is between about 90 g/L and about 110 g/L.

(28) Embodiment 15 is the method of any one of embodiments 1-14, wherein the solution is an aqueous

solution.

(29) Embodiment 16 is the method of any one of embodiments 1-15, wherein the solution is free of added surfactant.

(30) Embodiment 17 is the method of any one of embodiments 1-16, wherein a temperature of the air is between about 50° C. and about 100° C.

(31) Embodiment 18 is the method of any one of embodiments 1-17, wherein the glycerophospholipid layer comprises one or more open bilayers.

(32) Embodiment 19 is the method of embodiment 18, wherein one or more of the open bilayers are lamellar.

(33) Embodiment 20 is the method of any one of embodiments 1-17, wherein the glycerophospholipid layer comprises one or more closed bilayers.

(34) Embodiment 21 is the method of embodiment 20, wherein one or more of the closed bilayers are cylindrical.

(35) Embodiment 22 is the method of embodiment 20, wherein one or more of the closed bilayers are spherical.

(36) Embodiment 23 is the method of any one of embodiments 1-22, wherein a thickness of the layer is less than about 2 microns.

(37) Embodiment 24 is the method of any one of embodiments 1-22, wherein a thickness of the layer is less than about 1 micron.

(38) Embodiment 25 is a method of reducing the respiration rate of an agricultural product, the method comprising: applying a solution comprising one or more glycerophospholipids to a surface of the agricultural product, wherein a temperature of the solution is between about 10° C. and about 80° C.; and drying the solution on the surface of the agricultural product under a flow of air having a temperature between about 20° C. and about 100° C. to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a glycerophospholipid layer on the agricultural product.

(39) Embodiment 26 is a method of reducing the mass loss rate of an agricultural product, the method comprising: applying a solution comprising one or more glycerophospholipids to a surface of the agricultural product, wherein a temperature of the solution is between about 10° C. and about 80° C.; and drying the solution on the surface of the agricultural product under a flow of air having a temperature between about 20° C. and about 100° C. to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a glycerophospholipid layer on the agricultural product.

(40) Embodiment 27 is a method of preparing an agricultural product having a coating disposed thereon, the method comprising: applying a solution comprising one or more glycerophospholipids to a surface of the agricultural product, wherein a temperature of the solution is between about 10° C. and about 80° C.; and drying the solution on the surface of the agricultural product under a flow of air having a temperature between about 20° C. and about 100° C. to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a glycerophospholipid layer on the agricultural product.

(41) Embodiment 28 is a coated agricultural product comprising: an agricultural product; and a coating on the surface of the agricultural product, wherein the coating comprises: one or more glycerophospholipids, and a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product.

(42) Embodiment 29 is the coated agricultural product of embodiment 28, wherein the one or more glycerophospholipids comprise one or more of phosphatidylcholine, phosphatidylethanolamine, phosphatidylinositol, phosphatidylserine, and phosphatidic acid.

(43) Embodiment 30 is the coated agricultural product of embodiment 28 or embodiment 29, wherein the one or more glycerophospholipids comprise one or more compounds of Formula I:

(44) ##STR00008##

wherein: R.sup.1 is —H or one of the following fragments:

(45) ##STR00009##

and R.sup.2 and R.sup.3 are each independently, at each occurrence, —H or a fragment represented by Formula II:

(46) ##STR00010##

wherein: R.sup.4, R.sup.5, R.sup.8, R.sup.9, R.sup.12, R.sup.13, R.sup.14, R.sup.15 and R.sup.16 are each independently, at each occurrence, —H, —OH, —OR.sup.17 or C.sub.1-C.sub.6 alkyl; R.sup.6, R.sup.7, R.sup.10, and R.sup.11 are each independently, at each occurrence, —H, —OR.sup.17, or C.sub.1-C.sub.6 alkyl; and/or R.sup.4 and R.sup.5 can combine with the carbon atoms to which they are attached to form

C=O; and/or R.sup.8 and R.sup.9 can combine with the carbon atoms to which they are attached to form C=O; and/or R.sup.12 and R.sup.13 can combine with the carbon atoms to which they are attached to form C=O; and R.sup.17 is at each occurrence C.sub.1-C.sub.6 alkyl, the symbol  custom character represents a single bond or a cis or trans double bond; n is 0, 1, 2, 3, 4, 5, 6, 7 or 8; m is 0, 1, 2 or 3; q is 0, 1, 2, 3, 4 or 5; and r is 0, 1, 2, 3, 4, 5, 6, 7 or 8.

(47) Embodiment 31 is the coated agricultural product of embodiment 30, wherein the fragment represented by Formula II is one of:

(48) ##STR00011## ##STR00012## ##STR00013## ##STR00014##

(49) Embodiment 32 is the coated agricultural product of any one of embodiments 28-31, wherein the one or more glycerophospholipids comprise phosphatidylcholine, phosphatidylethanolamine, and phosphatidylinositol.

(50) Embodiment 33 is the coated agricultural product of embodiment 32, wherein the one or more glycerophospholipids comprise 20 wt % to 40 wt % phosphatidylcholine, 20 wt % to 40 wt % phosphatidylethanolamine, and 20 wt % to 40 wt % phosphatidylinositol.

(51) Embodiment 34 is the coated agricultural product of embodiment 32 or embodiment 33, wherein the one or more glycerophospholipids further comprise phosphatidylserine.

(52) Embodiment 35 is the coated agricultural product of embodiment 34, wherein the one or more glycerophospholipids comprise less than 5 wt % phosphatidylserine.

(53) Embodiment 36 is the coated agricultural product of any one of embodiments 28-35, wherein the multiplicity of glycerophospholipid bilayers comprises one or more open bilayers.

(54) Embodiment 37 is the coated agricultural product of embodiment 36, wherein one or more of the open bilayers are lamellar.

(55) Embodiment 38 is the coated agricultural product of any one of embodiments 28-35, wherein the multiplicity of glycerophospholipid bilayers comprises one or more closed bilayers.

(56) Embodiment 39 is the coated agricultural product of embodiment 38, wherein one or more of the closed bilayers are cylindrical.

(57) Embodiment 40 is the coated agricultural product of embodiment 38, wherein one or more of the closed bilayers are spherical.

(58) Embodiment 41 is the coated agricultural product of any one of embodiments 28-40, wherein a thickness of the coating is less than 2 microns.

(59) Embodiment 42 is the coated agricultural product of any one of embodiments 28-40, wherein a thickness of the coating is less than 1 micron.

(60) The details of one or more embodiments of the subject matter of this disclosure are set forth in the accompanying drawings and the description. Other features, aspects, and advantages of the subject matter will become apparent from the description, the drawings, and the claims.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 shows a plot of mass loss factors (MLF) for an agricultural product that is untreated, an agricultural product that is coated with a coating agent comprising one or more monoglycerides, and an agricultural product that is coated with a coating agent comprising one or more glycerophospholipids.

(2) FIG. 2 shows a plot of respiration rates for an agricultural product that is untreated, an agricultural product that is coated with a coating agent comprising one or more monoglycerides, and an agricultural product that is coated with a coating agent comprising one or more glycerophospholipids.

(3) FIG. 3 shows a plot of intensity vs. $q(\text{\AA}^{-1})$ from the x-ray scattering image of a coating on a polystyrene substrate.

(4) FIG. 4 shows a plot of mass loss factors for agricultural products that are treated with various coating agents.

(5) FIG. 5 shows a plot of respiration rates for agricultural products that are treated with various coating agents.

(6) FIG. 6 shows plots of intensity vs. $q(\text{\AA}^{-1})$ from the x-ray scattering image of coatings applied at varying concentrations on a polystyrene substrate.

(7) FIG. 7 shows plots of intensity vs. $q(\text{\AA}^{-1})$ from the x-ray scattering image of coatings applied at varying concentrations on a polystyrene substrate.

(8) FIG. 8 shows plots of intensity vs. $q(\text{\AA}^{-1})$ from the out-of-plane ($\perp$) and in-plane ($\parallel$) x-ray scattering image of a coating applied on a polystyrene substrate.

(9) FIG. 9 shows a plot of mass loss factors for agricultural products that are treated with various coating agents.

(10) FIG. 10 shows plots of intensity vs. $q(\text{\AA}^{-1})$ from the x-ray scattering image of a non-hydrogenated phosphatidylcholine (PC) coating and a hydrogenated phosphatidylcholine coating applied on a polystyrene substrate.

(11) FIG. 11 shows a plot of intensity vs. $q(\text{\AA}^{-1})$ from the x-ray scattering image of a hydrogenated phosphatidylcholine coating applied on a polystyrene substrate.

(12) FIG. 12 shows a plot of intensity vs. $q(\text{\AA}^{-1})$ from the x-ray scattering image of a non-hydrogenated phosphatidylcholine coating applied on a polystyrene substrate.

(13) FIG. 13 shows a plot of intensity vs. $q(\text{\AA}^{-1})$ from the x-ray scattering image of coatings applied on a polystyrene substrate.

DETAILED DESCRIPTION

Definitions

(14) As used herein, the term “plant matter” refers to any portion of a plant, including, for example, fruits (in the botanical sense, including fruit peels and juice sacs), vegetables, leaves, stems, barks, seeds, flowers, peels, or roots. Plant matter includes pre-harvest plants or portions thereof as well as post-harvest plants or portions thereof, including, e.g., harvested fruits and vegetables, harvested roots and berries, and picked flowers.

(15) As used herein, a “coating agent” refers to a composition including a compound or group of compounds from which a protective coating can be formed.

(16) As used herein, the “mass loss rate” refers to the rate at which the product loses mass (e.g., by releasing water and other volatile compounds). The mass loss rate is typically expressed as a percentage of the original mass per unit time (e.g., percent per day).

(17) As used herein, the term “mass loss factor” is defined as the ratio of the average mass loss rate of uncoated produce (measured for a control group) to the average mass loss rate of the corresponding tested produce (e.g., coated produce) over a given time. Hence a larger mass loss factor for a coated produce corresponds to a greater reduction in average mass loss rate for the coated produce.

(18) As used herein, the term “respiration rate” refers to the rate at which the product releases gas, such as CO_2 . This rate can be determined from the volume of gas (e.g., CO_2) (at standard temperature and pressure) released per unit time per unit mass of the product. The respiration rate can be expressed as $\text{ml gas/kg.Math.hour}$. The respiration rate of the product can be measured by placing the product in a closed container of known volume that is equipped with a sensor, such as a CO_2 sensor, recording the gas concentration within the container as a function of time, and then calculating the rate of gas release required to obtain the measured concentration values.

(19) As used herein, the term “respiration factor” is defined as the ratio of the average gas diffusion (e.g., CO_2 release) of uncoated produce (measured for a control group) to the average gas diffusion of the corresponding tested produce (e.g., coated produce) over a given time. Hence a larger respiration factor for a coated produce corresponds to a greater reduction in gas diffusion/respiration for the coated produce.

(20) As used herein, the term “contact angle” of a liquid on a solid surface refers to an angle of the outer surface of a droplet of the liquid measured where the liquid-vapor interface meets the liquid-solid interface. The contact angle quantifies the wettability of the solid surface by the liquid.

(21) As used herein, the terms “wetting agent” or “surfactant” each refer to a compound that, when added to a solvent, suspension, colloid, or solution, reduces the difference in surface energy between the solvent/suspension/colloid/solution and a solid surface on which the solvent/suspension/colloid/solution is disposed.

(22) As used herein, a “lipid bilayer” or “bilayer structure” refers to a structure which includes two contiguous sublayers, wherein each sublayer comprises molecules of glycerophospholipids aligned adjacent to each other lengthwise such that the hydrophilic ends form a hydrophilic surface and the hydrophobic ends form a hydrophobic surface; and the molecular arrangement defines a repeating lattice structure. The hydrophobic surfaces of each sublayer in the lipid bilayer face each other, and the hydrophilic surfaces of each layer face away from each other. A lipid bilayer can be an “open bilayer,” wherein each sublayer is arranged in a parallel sheet. For example, an open bilayer can have a lamellar structure. A lipid bilayer can also be a “closed bilayer,” wherein each sublayer is arranged in a circular structure. For example, a closed bilayer can have a spherical or cylindrical structure.

(23) As used herein, “lamellar structure” refers to a structure comprising lamella(e) vertically stacked adjacent to each other and held together by intermolecular forces. As used herein, “lamella(e)” refers to one lamella or two or more lamellae, that is, one or more discrete layers of molecules, respectively. In some embodiments, the molecules present in the lamella(e) are ordered (e.g., aligned, as in an open bilayer). The distance between a surface of a lamella and the surface of an adjacent lamella that is facing the same direction is referred to herein as “interlayer spacing” or “periodic spacing”. Interlayer spacing between two lamellae is determined by (1) obtaining an out-of-plane X-ray scattering image of a coating, (2) determining the scattering vector (q) of the peak corresponding to the lamellar structure, and (3) using Bragg's equation below, determine the interlayer spacing (d):

$$d=2\pi/q.\text{sub.peak} \quad (1)$$

(24) As used herein, “grain” refers to a domain within a polycrystalline structure wherein the lattice formation is continuous and has one orientation. The boundaries between the grains in a polycrystalline structure are defects in the lattice formation wherein the continuity of the lattice formation and/or orientation of the molecules forming the lattice formation are interrupted. The “grain size” of the grains that form a coating is determined by (1) obtaining an in-plane X-ray scattering image of the coating; (2) determining the full width at half maximum (FWHM) of the peak corresponding to the molecules in the coating; and (3) using the Scherrer equation below to calculate the grain size (D):

$$D=2\pi b/\text{FWHM} \quad (2)$$

where b=about 0.95 for a 2-dimensional crystal.

(25) Without being bound by any theory, grain size inversely correlates with grain boundaries. As such, the larger the grain size, the fewer the grain boundaries; and the smaller the grain size, the more grain boundaries there are. It is further understood that the fewer the grain boundaries in a coating, the lower the mass loss rate and/or respiration rate of the coated agricultural product since there are fewer pathways for water and/or gas to pass through the coating.

(26) As used herein, “mosaicity” refers to the probabilities that the orientation of crystal planes in a polycrystalline structure (e.g., a coating) deviate from a plane that is substantially parallel with the plane of the substrate (e.g., agricultural product) surface. Deviation of a crystal plane from a plane that is substantially parallel with the plane of the substrate surface is understood to be a type of crystal defect that increases the permeability of a coating to air and water, thus increasing the mass loss rate and respiration rate when the coating is disposed over an agricultural product.

(27) As used herein, “substrate” refers to an article that a coating is applied to. In some embodiments, the substrate is an agricultural product (e.g., produce), a silicon substrate, a polystyrene substrate, or a substrate comprising a polysaccharide (e.g., cellulose).

(28) Protective Coatings

(29) Described herein are solutions, suspensions, or colloids containing a composition (e.g., a coating agent) in a solvent that can be used to form protective coatings over substrates such as plant matter, agricultural products, or food products. The protective coatings can, for example, prevent or reduce water loss and gas diffusion from the substrates, oxidation of the substrates, and/or can shield the substrates from threats such as bacteria, fungi, viruses, and the like. The coatings can also protect the substrates from physical damage (e.g., bruising) and photodamage. Accordingly, the coating agents, solutions/suspensions/colloids, and the coatings formed thereof can be used to help store agricultural or other food products for extended periods of time without spoiling. In some instances, the coatings and the coating agents from which they are formed can allow for food to be kept fresh in the absence of refrigeration. The coating agents and coatings described herein can also be edible (i.e., the coating agents and coatings can be non-toxic for human consumption). In some particular implementations, the solutions/suspensions/colloids include a wetting agent or surfactant which cause the solution/suspension/colloid to better spread over the entire surface of the substrate during application, thereby improving surface coverage as well as overall performance of the resulting coating. In some particular implementations, the solutions/suspensions/colloids include an emulsifier which improves the solubility of the coating agent in the solvent and/or allows the coating agent to be suspended or dispersed in the solvent. The wetting agent and/or emulsifier can each be a component of the coating agent, or can be separately added to the solution/suspension/colloid. In some embodiments, the coatings include lamellar structures formed on the surface of the substrate (e.g., agricultural product) over which the coating is disposed. In some embodiments, the coatings include cylindrical structures formed on the surface of the substrate (e.g., agricultural product) over which the coating is disposed.

(30) Plant matter (e.g., agricultural products) and other degradable items can be protected against degradation

from biotic or abiotic stressors by forming a protective coating over the outer surface of the product. The coating can be formed by adding the constituents of the coating (herein collectively a “coating agent”) to a solvent (e.g., water and/or ethanol) to form a mixture (e.g., a solution, suspension, or colloid), applying the mixture to the outer surface of the product to be coated, e.g., by dipping the product in the mixture or by brushing or spraying the mixture over the surface of the product, and then removing the solvent from the surface of the product, e.g., by allowing the solvent to evaporate, thereby causing the coating to be formed from the coating agent over the surface of the product. The coating agent can be formulated such that the resulting coating provides a barrier to water and/or oxygen transfer, thereby preventing water loss from and/or oxidation of the coated product. The coating agent can additionally or alternatively be formulated such that the resulting coating provides a barrier to CO₂, ethylene and/or other gas transfer.

(31) Coating agents including a glycerophospholipid can both be safe for human consumption and can be used as coating agents to form coatings that are effective at reducing the ripening rate and reducing mass loss and oxidation in a variety of produce.

(32) Coating and Coating Agent Compositions

(33) In some embodiments, the compositions (e.g., the coating agents or coatings) comprise one or more glycerophospholipids. Exemplary classes of glycerophospholipids include phosphatidylcholine, phosphatidylethanolamine, phosphatidylinositol, phosphatidylserine, and phosphatidic acid. In some embodiments, the one or more glycerophospholipids comprise one or more of phosphatidylcholine, phosphatidylethanolamine, phosphatidylinositol, phosphatidylserine, and phosphatidic acid.

(34) In some embodiments, the one or more glycerophospholipids comprise one or more compounds of Formula I, where Formula I is:

(35) ##STR00015##

wherein: R^{sup.1} is —H or one of the following fragments:

(36) ##STR00016##

and R^{sup.2} and R^{sup.3} are each independently, at each occurrence, —H or a fragment represented by Formula II, where Formula II is:

(37) ##STR00017## wherein: R^{sup.4}, R^{sup.5}, R^{sup.8}, R^{sup.9}, R^{sup.12}, R^{sup.13}, R^{sup.14}, R^{sup.15} and R^{sup.16} are each independently, at each occurrence, —H, —OH, —OR^{sup.17} or C_{sub.1}-C_{sub.6} alkyl; R^{sup.6}, R^{sup.7}, R^{sup.10}, and R^{sup.11} are each independently, at each occurrence, —H, —OR^{sup.17}, or C_{sub.1}-C_{sub.6} alkyl; and/or R^{sup.4} and R^{sup.5} can combine with the carbon atoms to which they are attached to form C=O; and/or R^{sup.8} and R^{sup.9} can combine with the carbon atoms to which they are attached to form C=O; and/or R^{sup.12} and R^{sup.13} can combine with the carbon atoms to which they are attached to form C=O; and R^{sup.17} is at each occurrence C_{sub.1}-C_{sub.6} alkyl, the symbol

 custom character represents a single bond or a cis or trans double bond; n is 0, 1, 2, 3, 4, 5, 6, 7 or 8; m is 0, 1, 2 or 3; q is 0, 1, 2, 3, 4 or 5; and r is 0, 1, 2, 3, 4, 5, 6, 7 or 8.

(38) In some embodiments, the compositions (e.g., the coating agents or coatings) comprise one or more glycerophospholipids comprising one or more of the following fragments of Formula II:

(39) ##STR00018## ##STR00019## ##STR00020## ##STR00021##

(40) In some embodiments, the compound of Formula I is a compound of Formula Ia:

(41) ##STR00022##

(42) In some embodiments, the compound of Formula I is a compound of Formula Ib:

(43) ##STR00023##

(44) In some embodiments, the one or more glycerophospholipids comprise a racemic mixture of the compounds of Formula Ia and Formula Ib.

(45) In some embodiments, the one or more glycerophospholipids comprise phosphatidylcholine. In some embodiments, the phosphatidylcholine is a compound of Formula I wherein R^{sup.1} is

(46) ##STR00024##

In some embodiments, the one or more glycerophospholipids comprise about 1% to about 99% by weight of phosphatidylcholine, for example, about 5% to about 75%, about 10% to about 65%, about 15% to about 50%, or about 20% to about 40% by weight of phosphatidylcholine.

(47) In some embodiments, the one or more glycerophospholipids comprise phosphatidylethanolamine. In some embodiments, the phosphatidylethanolamine is a compound of Formula I wherein R^{sup.1} is

(48) ##STR00025##

In some embodiments, the one or more glycerophospholipids comprise about 1% to about 50% by weight of phosphatidylethanolamine, for example, about 5% to about 50%, about 10% to about 45%, about 15% to

about 40%, or about 20% to about 40% by weight of phosphatidylethanolamine.

(49) In some embodiments, the one or more glycerophospholipids comprise phosphatidylinositol. In some embodiments, the phosphatidylinositol is a compound of Formula 1 wherein R^{sup.1} is

(50) ##STR00026##

In some embodiments, the one or more glycerophospholipids comprise about 1% to about 50% by weight of phosphatidylinositol, for example, about 5% to about 50%, about 10% to about 45%, about 15% to about 40%, or about 20% to about 40% by weight of phosphatidylinositol.

(51) In some embodiments, the one or more glycerophospholipids comprise phosphatidylcholine, phosphatidylethanolamine, and phosphatidylinositol. In some embodiments, the one or more glycerophospholipids comprise about 20% to about 40% by weight of phosphatidylcholine, about 20% to about 40% by weight phosphatidylethanolamine, and about 20% to about 40% by weight phosphatidylinositol.

(52) In some embodiments, the one or more glycerophospholipids comprise phosphatidylserine. In some embodiments, the phosphatidylserine is a compound of Formula I wherein R^{sup.1} is

(53) ##STR00027##

In some embodiments, the one or more glycerophospholipids comprise less than about 25% by weight phosphatidylserine, for example less than about 15%, less than about 10%, or less than about 5% by weight phosphatidylserine.

(54) In some embodiments, the one or more glycerophospholipids comprise phosphatidylglycerol. In some embodiments, the phosphatidylglycerol is a compound of Formula I wherein R^{sup.1} is

(55) ##STR00028##

In some embodiments, the one or more glycerophospholipids comprises less than about 25% by weight phosphatidylglycerol, for example, less than about 15%, less than about 10%, or less than about 5% by weight phosphatidylglycerol.

(56) In some embodiments, the one or more glycerophospholipids comprise phosphatidylcholine, phosphatidylethanolamine, phosphatidylinositol, phosphatidyl glycerol, and phosphatidylserine. In some embodiments, the one or more glycerophospholipids comprise about 20% to about 40% by weight of phosphatidylcholine, about 20% to about 40% by weight phosphatidylethanolamine, about 20% to about 40% by weight phosphatidylinositol, and less than about 5% by weight phosphatidylserine.

(57) In some embodiments, the coating agent further comprises a phytosterol. In some embodiments, a weight ratio of the phytosterol to a total amount of the one or more glycerophospholipids is less than about 0.2, for example, less than about 0.15, 0.1, or 0.05.

(58) Coating Agent Mixtures

(59) In some embodiments, the composition (e.g., coating agent) can be dissolved, mixed, dispersed, or suspended in a solvent to form a mixture (e.g., solution, suspension, or colloid). Examples of solvents that can be used include water, methanol, ethanol, isopropanol, butanol, acetone, ethyl acetate, chloroform, acetonitrile, tetrahydrofuran, diethyl ether, methyl tert-butyl ether, and combinations thereof. In one example, the solvent is water. In one example, the solvent is ethanol. In some embodiments, the composition is dissolved or suspended in water to form an aqueous solution.

(60) In some embodiments, the concentration of the composition (e.g., coating agent) in the solution or mixture (e.g., solution, suspension, or colloid) is about 10 mg/mL to about 200 mg/mL, for example, about 10 to about 150 mg/mL, about 10 to about 120 mg/mL, about 10 to about 100 mg/mL, about 20 to about 200 mg/mL, about 20 to about 175 mg/mL, about 20 to about 150 mg/mL, about 20 to about 100 mg/mL, about 30 to about 175 mg/mL, about 30 to about 200 mg/mL, about 30 to about 175 mg/mL, about 30 to about 150 mg/mL, about 30 to about 120 mg/mL, about 30 to about 100 mg/mL, about 40 to about 175 mg/mL, about 50 mg/mL to about 150 mg/mL, about 80 mg/mL to about 120 mg/mL, or about 90 mg/mL to about 110 mg/mL. In one example, the concentration of the composition (e.g., coating agent) in the mixture (e.g., solution, suspension, or colloid) is about 100 mg/mL.

(61) In some embodiments, the concentration of the composition is less than 200 mg/mL, or less than 175 mg/mL. In some examples, phase separation and/or precipitation, which can affect the appearance and applicability of the coating, can occur at concentrations greater than 200 mg/mL.

(62) As previously described, coating agents can be formed predominantly of various combinations of glycerophospholipids. As also previously described, the coatings can be formed over the outer surface of the agricultural product by dissolving, suspending, or dispersing the coating agent in a solvent to form a mixture, applying the mixture to the surface of the agricultural product (e.g., by spray coating the product, by dipping the product in the mixture, or by brushing the mixture onto the surface of the product), and then removing the

solvent (e.g., by allowing the solvent to evaporate). The solvent can include any polar, non-polar, protic, or aprotic solvents, including any combinations thereof. Examples of solvents that can be used include water, methanol, ethanol, isopropanol, butanol, acetone, ethyl acetate, chloroform, acetonitrile, tetrahydrofuran, diethyl ether, methyl tert-butyl ether, any other suitable solvent, and combinations thereof. In cases where the coating is to be applied to plants or other edible products, it may be preferable to use a solvent that is safe for consumption, for example water, ethanol, or combinations thereof. Depending on the solvent that is used, the solubility limit of the coating agent in the solvent may be lower than desired for particular applications.

(63) In order to improve the solubility of the coating agent in the solvent, or to allow the coating agent to be suspended or dispersed in the solvent, the coating agent can further include an emulsifier. When the coatings are to be formed over plants or other edible products, it may be preferable that the emulsifier be safe for consumption. Furthermore, it may also be preferable that the emulsifier either not be incorporated into the coating or, if the emulsifier is incorporated into the coating, that it does not degrade the performance of the coating.

(64) As described above, the coating agent can be added to or dissolved, suspended, or dispersed in a solvent to form a colloid, suspension, or solution. The various components of the coating agent (e.g., one or more glycerophospholipids) can be combined prior to being added to the solvent and then added to the solvent together. Alternatively, the components of the coating agent can be kept separate from one another and then be added to the solvent consecutively (or at separate times).

(65) In some embodiments, the coating solutions/suspensions/colloids can further include a wetting agent that serves to reduce the contact angle between the solution/suspension/colloid and the surface of the substrate being coated. The wetting agent can be included as a component of the coating agent and therefore added to the solvent at the same time as other components of the coating agent. Alternatively, the wetting agent can be separate from the coating agent and can be added to the solvent either before, after, or at the same time as the coating agent. Alternatively, the wetting agent can be separate from the coating agent, and can be applied to a surface before the coating agent in order to prime the surface.

(66) In some embodiments, the coating solution/suspension/colloid is free of added wetting agent or surfactant.

(67) In some embodiments, the mixture or composition (e.g., coating or coating agent) comprises one or more (e.g., 1, 2, or 3) preservatives. In some embodiments, the one or more preservatives comprise one or more antioxidants, one or more antimicrobial agents, one or more chelating agents, or any combination thereof. Exemplary preservatives include, but are not limited to, vitamin E, vitamin C, butylatedhydroxyanisole (BHA), butylatedhydroxytoluene (BHT), sodium benzoate, disodium ethylenediaminetetraacetic acid (EDTA), citric acid, benzyl alcohol, benzalkonium chloride, butyl paraben, chlorobutanol, meta cresol, chlorocresol, methyl paraben, phenyl ethyl alcohol, propyl paraben, phenol, benzoic acid, sorbic acid, methyl paraben, propyl paraben, bronidol, and propylene glycol.

(68) Any of the coating solutions/suspensions/colloids described herein can further include an antimicrobial agent, for example ethanol or citric acid. In some embodiments, the antimicrobial agent is part of or a component of the solvent. Any of the coating solutions described herein can further include other components or additives such as sodium bicarbonate.

(69) Any of the coating agents described herein can further include additional materials that are also transported to the surface with the coating, or are deposited separately and are subsequently encapsulated by the coating (e.g., the coating is formed at least partially around the additional material), or are deposited separately and are subsequently supported by the coating (e.g., the additional material is anchored to the external surface of the coating). Examples of such additional materials can include cells, biological signaling molecules, vitamins, minerals, pigments, aromas, enzymes, catalysts, antifungals, antimicrobials, and/or time-released drugs. The additional materials can be non-reactive with surface of the coated product and/or coating, or alternatively can be reactive with the surface and/or coating.

(70) In some embodiments, the coating can include an additive configured, for example, to modify the viscosity, vapor pressure, surface tension, or solubility of the coating. The additive can, for example, be configured to increase the chemical stability of the coating. For example, the additive can be an antioxidant configured to inhibit oxidation of the coating. In some embodiments, the additive can reduce or increase the melting temperature or the glass-transition temperature of the coating. In some embodiments, the additive is configured to reduce the diffusivity of water vapor, oxygen, CO₂, or ethylene through the coating or enable the coating to absorb more ultra violet (UV) light, for example to protect the agricultural product (or any of the other products described herein). In some embodiments, the additive can be configured to provide

an intentional odor, for example a fragrance (e.g., smell of flowers, fruits, freshness, scents, etc.). In some embodiments, the additive can be configured to provide color and can include, for example, a dye or a US Food and Drug Administration (FDA) approved color additive.

(71) Any of the coating agents or coatings formed thereof that are described herein can be flavorless or have high flavor thresholds, e.g., above 500 ppm, and can be odorless or have a high odor threshold. In some embodiments, the materials included in any of the coatings described herein can be substantially transparent. For example, the coating agent, the solvent, and/or any other additives included in the coating can be selected so that they have substantially the same or similar indices of refraction. By matching their indices of refraction, they may be optically matched to reduce light scattering and improve light transmission. For example, by utilizing materials that have similar indices of refraction and have a clear, transparent property, a coating having substantially transparent characteristics can be formed.

(72) Any of the coatings described herein can be disposed on the external surface of an agricultural product or other substrate using any suitable means. For example, the substrate can be dip-coated in a bath of the coating formulation (e.g., an aqueous or mixed aqueous-organic or organic solution). The deposited coating can form a thin layer on the surface of an agricultural product, which can protect the agricultural product from biotic stressors, water loss, respiration, and/or oxidation. In some embodiments, the deposited coating can have a thickness of less than about 20 microns, 10 microns, 9 microns, 8 microns, 7 microns, 6 microns, 5 microns, 4 microns, 3 microns, 2 microns, or 1.5 microns. In some embodiments, the deposited coating can have a thickness of about 100 nm to about 20 microns, about 100 nm to about 2 microns, about 700 nm to about 1.5 microns, about 700 nm to about 1 micron, about 1 micron to about 1.6 microns, or about 1.2 microns to about 1.5 microns. In some embodiments, the coating is transparent to the naked eye.

(73) In some embodiments, the deposited coating can be deposited substantially uniformly over the substrate and can be free of defects and/or pinholes. In some embodiments, the dip-coating process can include sequential coating of the agricultural product in baths of coating precursors that can undergo self-assembly or covalent bonding on the agricultural product to form the coating. In some embodiments, the coating can be deposited on agricultural products by passing the agricultural products under a stream of the coating solution/suspension/colloid (e.g., a waterfall of the coating solution/suspension/colloid). For example, the agricultural products can be disposed on a conveyor that passes through the stream of the coating solution/suspension/colloid. In some embodiments, the coating can be misted, vapor- or dry vapor-deposited on the surface of the agricultural product. In some embodiments, the coating solution/suspension/colloid can be mechanically applied to the surface of the product to be coated, for example by brushing it onto the surface. In some embodiments, the coating can be configured to be fixed on the surface of the agricultural product by UV crosslinking or by exposure to a reactive gas, for example oxygen.

(74) In some embodiments, the coating solutions/suspensions/colloids can be spray-coated on the agricultural products. Commercially available sprayers can be used for spraying the coating solutions/suspensions/colloids onto the agricultural product. In some embodiments, the coating formulation can be electrically charged in the sprayer before spray-coating on to the agricultural product, such that the deposited coating electrostatically and/or covalently bonds to the exterior surface of the agricultural product.

(75) In some embodiments, coatings formed from coating agents described herein over agricultural products can be configured to change the surface energy of the agricultural product. Various properties of coatings described herein can be adjusted by tuning the crosslink density of the coating, its thickness, or its chemical composition. This can, for example, be used to control the ripening of postharvest fruit or produce. For example, coatings formed from coating agents that primarily include bifunctional or polyfunctional monomer units can, for example, have higher crosslink densities than those that include monofunctional monomer units. Thus, coatings formed from bifunctional or polyfunctional monomer units can in some cases result in slower rates of ripening as compared to coatings formed from monofunctional monomer units.

(76) As previously described, the coatings formed from coating agents described herein can be configured to prevent water loss or other moisture loss from the coated portion of the plant, delay ripening, and/or prevent oxygen diffusion into the coated portion of the plant, for example, to reduce oxidation of the coated portion of the plant. The coatings can also serve as a barrier to diffusion of carbon dioxide and/or ethylene into or out of the plant or agricultural product. The coatings can also protect the coated portion of the plant against biotic stressors, such as, for example, bacteria, fungi, viruses, and/or pests that can infest and decompose the coated portion of the plant. Since bacteria, fungi and pests all identify food sources via recognition of specific molecules on the surface of the agricultural product, coating the agricultural products with the coating agent can deposit molecularly contrasting molecules on the surface of the portion of the plant, which can render the

agricultural products unrecognizable. Furthermore, the coating can also alter the physical and/or chemical environment of the surface of the agricultural product making the surface unfavorable for bacteria, fungi or pests to grow. The coating can also be formulated to protect the surface of the portion of the plant from abrasion, bruising, or otherwise mechanical damage, and/or protect the portion of the plant from photodegradation. The portion of the plant can include, for example, a leaf, a stem, a shoot, a flower, a fruit, a root, etc.

(77) Any of the coatings described herein can be used to reduce the humidity generated by agricultural products (e.g., fresh produce) via mass loss (e.g., water loss) during transportation and storage by reducing the mass loss rate of the agricultural products (e.g., fresh produce).

(78) In some embodiments, the agricultural product is coated with a composition that reduces the mass loss rate by at least about 10%, 15%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 75%, 80%, 85%, 90% or greater compared to untreated product measured. In some embodiments, treating an agricultural product using any of the coatings described herein can give a mass loss factor of at least about 1.1, 1.2, 1.3, 1.4, 1.5, 1.6, 1.7, 1.8, 1.9, 2.0, 2.2, 2.4, 2.6, 2.8, or 3.0. In some embodiments, treating an agricultural product using any of the coatings described herein can reduce the humidity generated during storage by at least about 1%, 2%, 3%, 4%, 5%, 10%, 15%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 75%, 80%, 85%, 90% or greater compared to untreated product. In some embodiments, the reduction in mass loss rate of the agricultural product can reduce the energy required to maintain a relative humidity at a predetermined level (e.g., at about 90%, 85%, 80%, 75%, 70%, 65%, 60%, 55%, 50%, or 45% relative humidity or less) during storage or transportation. In some embodiments, the energy required to maintain a relative humidity at the predetermined level (e.g., any of the predetermined levels listed above) during storage or transportation can be reduced by at least about 1%, 2%, 3%, 4%, 5%, 10%, 15%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 75%, 80%, 85%, 90% or greater compared to untreated product.

(79) Any of the coatings described herein can be used to reduce the heat generated by agricultural products (e.g., fresh produce) via respiration during transportation and storage by reducing the respiration rate of the agricultural products (e.g., fresh produce). In some embodiments, the product is coated with a composition that reduces the respiration rate by at least about 10%, 15%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 75%, 80%, 85%, 90% or greater compared to untreated product (measured as described above). In some embodiments, the reduction in heat generated by the agricultural product can reduce the energy required to maintain a temperature (e.g., a predetermined temperature) during storage or transportation. In some embodiments, the heat generated can be reduced by at least about 5%, 10%, 15%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 75%, 80%, 85%, 90% or greater for coated products compared to untreated products. In some embodiments, the energy required to maintain the coated products at a predetermined temperature (e.g., at about 25° C., 23° C., 20° C., 18° C., 15° C., 13° C., 10° C., 8° C., 5° C., or 3° C. or less) can be reduced by at least about 1%, 2%, 3%, 4%, 5%, 10%, 15%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 75%, 80%, 85%, 90% or greater compared to untreated products.

(80) Respiration rate approximations for various types of agricultural products (e.g., fresh produce) are shown in Table 1.

(81) TABLE-US-00001 TABLE 1 Respiration rates for various agricultural products. Respiration Rate at 20° C. Produce Type (ml CO₂/kg .Math. hour) Apples 10-30 Apricot 15-25 Asparagus 138-250 Avocado 40-150 Bananas 20-70 Broccoli 140-160 Cantaloupe 23-33 Cherry 22-28 Corn 268-311 Cucumber 7-24 Fig 20-30 Grape 12-15 Grapefruit 7-12 Honeydew 20-27 Kiwifruit 15-20 Lemon 10-14 Lime 6-10 Mandarin 10-15 Mango 35-80 Orange 11-17 Papaya 15-35 (at 15° C.) Peach 32-55 Pear 15-35 Peas 123-180 Pineapple 15-20 Strawberry 50-100 Tomato 12-22 Watermelon 17-25

(82) In some embodiments, the methods and compositions described herein are used to treat agricultural products (e.g., fresh produce) that are stored and/or transported in a refrigerated container or “reefer”. Heat from produce respiration is a contributor to the overall heat within a refrigerated container. In some embodiments, the methods and compositions described herein can reduce the respiration rate of the treated agricultural products (e.g., fresh produce) in order to reduce the heat generated due to respiration of the agricultural products (e.g., fresh produce) in a refrigerated container or “reefer”. In some embodiments, the methods and compositions described herein can reduce the mass loss rate of the treated agricultural products (e.g., fresh produce) in order to reduce the humidity generated due to mass loss (e.g., water loss) of the agricultural products (e.g., fresh produce) in a refrigerated container or “reefer”.

(83) The methods and compositions described herein can also be used to minimize or reduce temperature or humidity gradients that arise from concentrating agricultural products (e.g., fresh produce) in stacks or pallets

in order to prevent uneven ripening. The treated agricultural products (e.g., fresh produce) can be straight stacked during storage or can be stacked in an alternative fashion (e.g., cross stacked) to increase circulation around the agricultural products (e.g., fresh produce). Within the produce supply chain, boxes of agricultural products may be reoriented from a straight stack, which can be preferable during shipment, to a cross stack, which can be used during storage to increase air circulation and to prevent uneven ripening.

(84) In some embodiments, treating an agricultural product with a coating that reduces the respiration rate can reduce the rate at which the temperature increases in a stack (e.g., upon removal from cold storage) by at least about 0.5° C. per day, for example, at least about 1.0° C., 1.5° C., 2.0° C., 2.5° C., 3.0° C., 3.5° C., 4.0° C., 4.5° C., or 5° C. per day, as compared to an untreated stack. In some embodiments, treating an agricultural product with a coating that reduces the respiration rate can reduce the equilibrium temperature difference between the atmosphere and the average temperature of the stack by at least about 0.5° C., 1.0° C., 1.5° C., 2.0° C., 2.5° C., 3.0° C., 3.5° C., 4.0° C., 4.5° C., or 5° C.

(85) Any of the coatings described herein can be used to protect any agricultural product. In some embodiments, the coating can be coated on an edible agricultural product, for example, fruits, vegetables, edible seeds and nuts, herbs, spices, produce, meat, eggs, dairy products, seafood, grains, or any other consumable item. In such embodiments, the coating can include components that are non-toxic and safe for consumption by humans and/or animals. For example, the coating can include components that are U.S. Food and Drug Administration (FDA) approved direct or indirect food additives, FDA approved food contact substances, satisfy FDA regulatory requirements to be used as a food additive or food contact substance, and/or is an FDA Generally Recognized as Safe (GRAS) material. Examples of such materials can be found within the FDA Code of Federal Regulations Title 21, located at

["www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfcfr/cfrsearch.cfm"](http://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfcfr/cfrsearch.cfm). In some embodiments, the components of the coating can include a dietary supplement or ingredient of a dietary supplement. The components of the coating can also include an FDA approved food additive or color additive. In some embodiments, the coating can include components that are naturally derived, as described herein. In some embodiments, the coating can be flavorless or have a high flavor threshold of below 500 ppm, are odorless or have a high odor threshold, and/or are substantially transparent. In some embodiments, the coating can be configured to be washed off an edible agricultural product, for example, with water.

(86) In some embodiments, the coatings described herein can be formed on an inedible agricultural product. Such inedible agricultural products can include, for example, inedible flowers, seeds, shoots, stems, leaves, whole plants, and the like. In such embodiments, the coating can include components that are non-toxic, but the threshold level for non-toxicity can be higher than that prescribed for edible products. In such embodiments, the coating can include an FDA approved food contact substance, an FDA approved food additive, or an FDA approved drug ingredient, for example, any ingredient included in the FDA's database of approved drugs, which can be found at ["http://www.accessdata.fda.gov/scripts/cder/drugsatfda/index.cfm"](http://www.accessdata.fda.gov/scripts/cder/drugsatfda/index.cfm). In some embodiments, the coating can include materials that satisfy FDA requirements to be used in drugs or are listed within the FDA's National Drug Discovery Code Directory,

["www.accessdata.fda.gov/scripts/cder/ndc/default.cfm"](http://www.accessdata.fda.gov/scripts/cder/ndc/default.cfm). In some embodiments, the materials can include inactive drug ingredients of an approved drug product as listed within the FDA's database,

["www.accessdata.fda.gov/scripts/cder/ndc/default.cfm"](http://www.accessdata.fda.gov/scripts/cder/ndc/default.cfm).

(87) Embodiments of the coatings described herein provide several advantages, including, for example: (1) the coatings can protect the agricultural products from biotic stressors, i.e. bacteria, viruses, fungi, or pests; (2) the coatings can prevent evaporation of water and/or diffusion of oxygen, carbon dioxide, and/or ethylene; (3) coating can help extend the shelf life of agricultural products, for example, post-harvest produce, without refrigeration; (4) the coatings can introduce mechanical stability to the surface of the agricultural products eliminating the need for expensive packaging designed to prevent the types of bruising which accelerate spoilage; (5) use of agricultural waste materials to obtain the coatings can help eliminate the breeding environments of bacteria, fungi, and pests; (6) the coatings can be used in place of pesticides to protect plants, thereby minimizing the harmful impact of pesticides to human health and the environment; (7) the coatings can be naturally derived and hence, safe for human consumption. Since in some cases the components of the coatings described herein can be obtained from agricultural waste, such coatings can be made at a relatively low cost. Therefore, the coatings can be particularly suited for small scale farmers, for example, by reducing the cost required to protect crops from pesticides and reducing post-harvest losses of agricultural products due to decomposition by biotic and/or environmental stressors.

(88) Solvents

(89) The solvent to which the coating agent and wetting agent (when separate from the coating agent) is added to form the solution/suspension/colloid can, for example, be water, methanol, ethanol, isopropanol, butanol, acetone, ethyl acetate, chloroform, acetonitrile, tetrahydrofuran, diethyl ether, methyl tert-butyl ether, an alcohol, any other suitable solvent, or a combination thereof. The resulting solutions, suspensions, or colloids can be suitable for forming coatings on agricultural products. For example, the solutions, suspensions, or colloids can be applied to the surface of the agricultural product, after which the solvent can be removed (e.g., by evaporation or convective drying), leaving a protective coating formed from the coating agent on the surface of the agricultural product.

(90) While a number of the solvents above (particularly water and ethanol) can be safely and effectively used in solutions/suspensions/colloids that are applied to edible products such as produce or other agricultural products, in many cases it can be advantageous to use either water or otherwise a solvent which is at least about 40% (and in many cases higher) water by volume. This is because water is typically cheaper than other suitable solvents and can also be safer to work with than solvents that have a higher volatility and/or a lower flash point (e.g., acetone or alcohols such as isopropanol or ethanol). In some embodiments, the solvent comprises water. For example, the solvent can be water. Accordingly, for any of the solutions/suspensions/colloids described herein, the solvent or solution/suspension/colloid can be at least about 40%, 45%, 50%, 55%, 60%, 65%, 70%, 75%, 80%, 85%, 90%, 95%, or 99% water by mass or by volume. In some embodiments, the solvent includes a combination of water and ethanol, and can optionally be at least about 40%, 45%, 50%, 55%, 60%, 65%, 70%, 75%, 80%, 85%, 90%, 95%, or 99% water by volume. In some embodiments, the solvent or solution/suspension/colloid is about 40% to about 100%, about 40% to about 99%, about 40% to about 95%, about 40% to about 90%, about 40% to about 85%, about 40% to about 80%, about 50% to about 100%, about 50% to about 99%, about 50% to about 95%, about 50% to about 90%, about 50% to about 85%, about 50% to about 80%, about 60% to about 100%, about 60% to about 99%, about 60% to about 95%, about 60% to about 90%, about 60% to about 85%, about 60% to about 80%, about 70% to about 100%, about 70% to about 99%, about 70% to about 95%, about 70% to about 90%, about 70% to about 85%, about 80% to about 100%, about 80% to about 99%, about 80% to about 97%, about 80% to about 95%, about 80% to about 93%, about 80% to about 90%, about 85% to about 100%, about 85% to about 99%, about 85% to about 97%, about 85% to about 95%, about 90% to about 100%, about 90% to about 99%, about 90% to about 98%, or about 90% to about 97% water by mass or volume.

(91) In view of the above, for some applications the solvent can be a low wetting solvent (i.e., a solvent exhibiting a large contact angle with respect to the surface to which it is applied). For example, in the absence of any added wetting agents or other surfactants, the contact angle between the solvent and either (a) carnauba wax, (b) candelilla wax, (c) paraffin wax, or (d) the surface of a non-waxed lemon can be at least about 70°, for example at least about 75°, 80°, 85°, or 90°. Addition of any of the wetting agents described herein to the solvent, either alone or in combination with other compounds or coating agents, can cause the contact angle between the resulting solution/suspension/colloid and either (a) carnauba wax, (b) candelilla wax, (c) paraffin wax, or (d) the surface of a non-waxed lemon to be less than about 85°, for example, less than about 80°, 75°, 70°, 65°, 60°, 55°, 50°, 45°, 40°, 35°, 30°, 25°, 20°, 15°, 10°, 5°, or 0°.

(92) The coating agent that is added to or dissolved, suspended, or dispersed in the solvent to form the coating solution/suspension/colloid can be any compound or combination of compounds capable of forming a protective coating over the substrate to which the solution/suspension/colloid is applied. The coating agent can be formulated such that the resulting coating protects the substrate from biotic and/or abiotic stressors. For example, the coating can prevent or suppress the transfer of oxygen and/or water, thereby preventing the substrate from oxidizing and/or from losing water via transpiration/osmosis/evaporation. In cases where the substrate is perishable and/or edible, for example when the substrate is a plant, an agricultural product, or a piece of produce, the coating agent is preferably composed of non-toxic compounds that are safe for consumption.

(93) Coated Agricultural Products and Methods of Preparation and Use Thereof

(94) In some embodiments, when the components of the coating agent (e.g., one or more glycerophospholipids) are mixed with a solvent, they form microstructures, such as, for example, vesicles in the solvent. In some embodiments, when this mixture contacts a surface, such as an agricultural product (e.g., produce), the microstructure can adsorb to the surface and form an open bilayer (e.g., lamella), or a series of stacked open bilayers to form an open bilayer structure (e.g., a lamellar structure) on the surface. In some embodiments, upon removal or drying of the solvent, the open bilayer structure partitions into grains, the boundaries between the grains being crystal defects. In some embodiments, when this mixture contacts a

surface, such as an agricultural product (e.g., produce), the microstructure can adsorb to the surface and form a closed bilayer (e.g., a sphere or a cylinder), or a series of closed bilayers to form a closed bilayer structure on the surface (e.g., a spherical or cylindrical structure). In some embodiments, upon removal or drying of the solvent, the closed bilayer structure partitions into grains, the boundaries between the grains being crystal defects.

(95) In some embodiments, an advantage of the open bilayer (e.g., a lamellar) structure is its low permeability. Without being bound by any theory, when water passes through the coating, it travels through grain boundaries and between the open bilayer structure if the outer surfaces of the open bilayer structure are sufficiently hydrophilic (e.g., when the lamellae are lipid bilayers). In some embodiments, the open bilayer structure composed of lipid bilayers formed from one or more glycerophospholipids in the coating increases the hydrophilicity of the outer surfaces of the lipid bilayers that make up the coating, thus allowing more water to intercalate between the lipid bilayers and therefore increasing the water permeability of the coating, resulting in an increased mass loss rate.

(96) In some embodiments, an advantage of the closed bilayer structure (e.g., a spherical or cylindrical structure) is its low permeability. Without being bound by any theory, when water passes through the coating, it travels through grain boundaries and between the closed bilayer structure if the outer surfaces of the closed bilayer structure are sufficiently hydrophilic (e.g., when the spherical or cylindrical structures are lipid bilayers). In some embodiments, the closed bilayer structure composed of lipid bilayers formed from one or more glycerophospholipids in the coating increases the hydrophilicity of the outer surfaces of the lipid bilayers that make up the coating, thus allowing more water to intercalate between the lipid bilayers and therefore increasing the water permeability of the coating, resulting in an increased mass loss rate.

(97) In some embodiments, increasing the concentration of the coating agent in the mixture increases the thickness of the coating, which, for example, can reduce the water permeability (and can therefore reduce mass loss when the coating is disposed over an agricultural product) and can lower the gas diffusion ratio (and can therefore reduce the respiration rate when the coating is disposed over an agricultural product).

(98) In some embodiments, the higher the temperature of drying, the larger the grain size and lower the mosaicity (which is a measure of the probabilities that the orientation of crystal planes in a coating deviate from a plane that is substantially parallel with the plane of the substrate surface, recognized as a type of crystal defect) in the coating, which can result in fewer grain boundaries and defects for water and/or gas to travel through. In some embodiments, this can result in a lower water and gas permeability that can translate into a lower mass loss rate and lower respiration rate when, e.g., the coating is disposed on an agricultural product.

(99) In some embodiments, heating the coating (or coated agricultural product) from a first temperature to a second temperature higher than the first temperature but below the melting point (i.e., the phase transition temperature) of the coating, then cooling the coating, can increase the grain size in the coating, which can result in a lower mass loss rate, lower gas diffusion ratio, and lower respiration rate.

(100) Coated Agricultural Products

(101) In one aspect, described herein is a coated substrate comprising a substrate and a coating comprising a glycerophospholipid layer having an open or closed glycerophospholipid bilayer structure formed on the substrate, wherein the coating has a thickness of less than about 20 microns. For example, the coating can have a thickness of less than about 10 microns, 5 microns, 2 microns, or 1 micron.

(102) In some embodiments, the glycerophospholipid layer comprises one or more open bilayers. For example, the open bilayer can be lamellar.

(103) In some embodiments, the glycerophospholipid layer comprises one or more closed bilayers. For example, the one or more closed bilayers can each independently be cylindrical or spherical.

(104) In another aspect, described herein is a coated substrate comprising a substrate and a coating comprising a lamellar structure formed on the substrate, wherein the coating comprises a plurality of grains. In another aspect, described herein is a coated substrate comprising a substrate and a coating comprising a spherical structure formed on the substrate, wherein the coating comprises a plurality of grains. In another aspect, described herein is a coated substrate comprising a substrate and a coating comprising a cylindrical structure formed on the substrate, wherein the coating comprises a plurality of grains.

(105) In some embodiments, the substrate is an agricultural product, a silicon substrate, a polystyrene substrate, or a substrate comprising a polysaccharide (e.g., cellulose). For example, the substrate can be an agricultural product.

(106) In another aspect, described herein is a coated agricultural product comprising an agricultural product and a coating comprising a lamellar structure formed on the agricultural product, wherein the coating has a

thickness of less than about 20 microns. In another aspect, described herein is a coated agricultural product comprising an agricultural product and a coating comprising a spherical structure formed on the agricultural product, wherein the coating has a thickness of less than about 20 microns. In another aspect, described herein is a coated agricultural product comprising an agricultural product and a coating comprising a cylindrical structure formed on the agricultural product, wherein the coating has a thickness of less than about 20 microns.

(107) In another aspect, described herein is a coated agricultural product comprising an agricultural product and a coating comprising a lamellar structure formed on the agricultural product, wherein the coating comprises a plurality of grains. In another aspect, described herein is a coated agricultural product comprising an agricultural product and a coating comprising a cylindrical structure formed on the agricultural product, wherein the coating comprises a plurality of grains. In another aspect, described herein is a coated agricultural product comprising an agricultural product and a coating comprising a spherical structure formed on the agricultural product, wherein the coating comprises a plurality of grains.

(108) In some embodiments (e.g., when the lamella is a lipid bilayer, such as a lipid bilayer comprising one or more glycerophospholipids)), the lattice formation is defined by a hexagonal unit cell. The distance (referred to as “a”) between each adjacent molecule in the unit cell is about 0.2 nm to about 2 nm, for example, about 0.2 to about 0.7 nm, about 0.2 to about 1.2 nm, about 0.2 nm to about 0.4 nm, about 0.3 nm to about 0.5 nm, about 0.4 nm to about 0.6 nm, about 0.43 nm to about 0.5 nm, or about 0.47 nm to about 0.48 nm. In some embodiments, the lattice formation is defined by an orthorhombic unit cell. In some embodiments, the lattice formation is defined by a tetragonal unit cell. In some embodiments, the lattice formation is defined by a monoclinic unit cell.

(109) In some embodiments, the lamellar structure comprises a plurality of lamellae. The distance between a surface of a lamella and the surface of an adjacent lamella that is facing the same direction is referred to herein as “periodic spacing.” In some embodiments, the interlayer spacing of the lamellae is about 1.0 to about 20 nm, for example, about 1 to about 20 nm, about 2 to about 13 nm, about 3 nm to about 10 nm, about 3 to about 7 nm, about 3 to about 6 nm, about 3 to about 5 nm, about 5 to about 7 nm, about 4 to about 6 nm, about 4 to about 5 nm, about 5 to about 6 nm, or about 5.0 to about 5.8 nm.

(110) In some embodiments, the coating comprises a plurality of grains.

(111) In some embodiments, the grain size is about 2 nm to about 100 nm, for example, about 4 nm to about 100 nm, about 7 nm to about 100 nm, about 6 nm to about 100 nm, about 6 nm to about 80 nm, about 6 nm to about 60 nm, about 6 nm to about 40 nm, about 6 nm to about 25 nm, about 9 nm to about 22 nm, about 9 nm to about 15 nm, about 13 nm to about 25 nm, about 8 nm to about 25 nm, about 11 nm to about 17 nm, about 11 nm to about 14 nm, about 13 nm to about 17 nm, about 12 nm to about 16 nm, about 15 nm to about 17 nm, about 9 nm to about 13 nm, about 13 nm to about 17 nm, about 17 nm to about 25 nm, about 2 nm to about 10 nm, 5 nm to about 10 nm, about 8 nm to about 9 nm, about 8.5 nm to about 9.5 nm, about 9 nm to about 10 nm, or about 8 nm, 9 nm, 10 nm, 11 nm, 12 nm, 13 nm, 14 nm, 15 nm, 16 nm, 17 nm, 19 nm, 21 nm, or 22 nm.

(112) Methods of Use and Application

(113) In one aspect, described herein is a method of coating a substrate, the method comprising: applying a solution comprising one or more glycerophospholipids to a surface of an agricultural product; and drying the solution on the surface of an agricultural product under a forced flow of air to form a glycerophospholipid layer on the agricultural product, wherein: the glycerophospholipid layer comprises a multiplicity of glycerophospholipid bilayers, and the glycerophospholipid layer has a thickness of less than about 2 microns.

(114) In another aspect, described herein is a method of coating a substrate, the method comprising: applying a solution comprising one or more glycerophospholipids to the surface of an agricultural product; and drying the solution on the surface of an agricultural product under a forced flow of air at a temperature of greater than about 50° C. to form a glycerophospholipid layer on the agricultural product, wherein: the glycerophospholipid layer comprises a multiplicity of glycerophospholipid bilayers, and each of the glycerophospholipid bilayers comprises a plurality of grains.

(115) In some embodiments, the temperature of the solution is between about 10° C. and about 80° C., for example, between about 10° C. and about 70° C., about 20° C. and about 80° C., about 20° C. and about 60° C., or about 40° C. and about 70° C.

(116) In some embodiments, the temperature of the air is between about 20° C. and about 120° C., for example, between about 20° C. and about 100° C., about 40° C. and about 120° C., or about 50° C. and about 100° C.

(117) In another aspect, described herein is a method of coating a substrate, the method comprising: applying a mixture comprising a coating agent and a solvent to the substrate; removing the solvent to form a coating on the substrate; heating the coated agricultural product from a first temperature to a second temperature, wherein the second temperature is greater than the first temperature and less than the melting point of the coating; and cooling the coated substrate from the second temperature to a third temperature, wherein the third temperature is less than the second temperature, wherein: the coating comprises a multiplicity of glycerophospholipid bilayers; and each of the glycerophospholipid bilayers comprises a plurality of grains.

(118) In some embodiments, the first temperature is about 0° C. to about 50° C., for example, about 10° C. to about 40° C., about 20° C. to about 30° C., about 23° C. to about 27° C., or about 25° C. In some embodiments, the first temperature is greater than the temperature of the surrounding atmosphere. In some embodiments, the first temperature is less than the temperature of the surrounding atmosphere.

(119) In some embodiments, the second temperature is about 40° C. to about 65° C., for example, about 45° C. to about 65° C., about 50° C. to about 65° C., about 55° C. to about 65° C., about 57° C. to about 63° C., or about 60° C. In some embodiments, the second temperature is greater than the temperature of the surrounding atmosphere. In some embodiments, the second temperature is less than the temperature of the surrounding atmosphere. In some embodiments, the coated agricultural product is heated with air having a temperature higher than the temperature of the agricultural product. In some embodiments, the air that the coated agricultural product is heated with is higher than the second temperature. In some embodiments, the air that the coated agricultural product is heated with is higher than the melting point of the coating.

(120) In some embodiments, if the coating is heated at or above its melting temperature (e.g., about 65° C. to about 70° C., or about 70° C.), the lattice formation of the crystal planes (e.g., lamellae) in the coating can be disrupted, the constituent molecules can adopt random orientations, and the coating can liquify.

(121) In some embodiments, the third temperature is about 0° C. to about 50° C., for example, about 10° C. to about 40° C., about 20° C. to about 30° C., about 23° C. to about 27° C., or about 25° C. In some embodiments, the third temperature is greater than the temperature of the surrounding atmosphere. In some embodiments, the third temperature is less than the temperature of the surrounding atmosphere.

(122) In some embodiments, the second temperature is maintained for about 5 seconds to about 10 hours. For example, the second temperature can be maintained for about 5 seconds to about 7 hours, about 5 seconds to about 3 hours, about 5 seconds to about 1.5 hours, about 5 seconds to about 60 minutes, about 30 seconds to about 45 minutes, about 5 minutes to about 60 minutes, about 10 minutes to about 45 minutes, about 20 minutes to about 40 minutes, about 25 minutes to about 35 minutes, about 30 seconds to about 10 minutes, about 30 seconds to about 7 minutes, about 30 seconds to about 3 minutes, about 3 minutes to about 7 minutes, about 30 seconds to about 1 minute, or about 1 minute to about 5 minutes.

(123) In some embodiments, the grain size after cooling the coated agricultural product from the second temperature to the third temperature is larger than the grain size before heating the coated agricultural product from the first temperature to the second temperature. In some embodiments, the grain size of the coating before heating the coated agricultural product from the first temperature to the second temperature is about 2 nm to about 10 nm, for example, about 5 nm to about 10 nm, about 8 nm to about 9 nm, about 8.5 nm to about 9.5 nm, or about 9 nm to about 10 nm. For example, the grain size of the coating after cooling the coated agricultural product from the second temperature to the third temperature can be about 7 nm to about 100 nm (e.g., about 8 nm to about 25 nm, about 11 nm to about 17 nm, about 11 nm to about 14 nm, about 13 nm to about 17 nm, about 12 nm to about 16 nm, or about 15 nm to about 17 nm).

(124) In another aspect, described herein is a method of reducing the mass loss rate of an agricultural product, the method comprising: applying a solution comprising one or more glycerophospholipids and a solvent to a surface of an agricultural product; and drying the solution on the surface of an agricultural product under a forced flow of air to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a glycerophospholipid layer on the agricultural product.

(125) In another aspect, described herein is a method of reducing the respiration rate of an agricultural product, the method comprising: applying a solution comprising one or more glycerophospholipids and a solvent to a surface of an agricultural product; and drying the solution on the surface of an agricultural product under a forced flow of air to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a glycerophospholipid layer on the agricultural product.

(126) In some embodiments, the mixture is dried at a temperature of about 20° C. to about 100° C., for example, about 25° C. to about 80° C., about 25° C. to about 70° C., about 30° C. to about 65° C., about 40° C. to about 65° C., 50° C. to about 65° C., about 55° C. to about 65° C., about 60° C. to about 65° C., about

55° C., about 60° C., or about 65° C. In some embodiments, the mixture is partially dried. In some embodiments, the drying removes greater than about 5% of the solvent, for example, greater than about 10%, 20%, 30%, 40%, 50%, 60%, 70%, 80%, 90%, or 95% of the solvent. In some embodiments, the bilayer structure forms when the mixture is partially dried. In some embodiments, the bilayer structure forms after at least 5% of the solvent has been removed, for example, after at least about 10%, 20%, 30%, 40%, 50%, 60%, 70%, 80%, 90%, or 95% of the solvent has been removed.

(127) In some embodiments, faster solvent removal and/or drying can improve the performance of the coating. For example, faster solvent removal and/or drying can result in thicker and more homogeneous coatings. In some embodiments, removing the solvent or drying the mixture is performed in under about 2 hours, for example, in under about 1.5 hours, 1 hour, 45 minutes, 30 minutes, 25 minutes, 20 minutes, 15 minutes, 10 minutes, 5 minutes, 4 minutes, 2 minutes, 1 minute, 30 seconds, 15 seconds, 10 seconds, 5 seconds, or 3 seconds.

(128) In another aspect, described herein is a method of coating an agricultural product, the method comprising: applying a solution comprising one or more glycerophospholipids and a solvent to a surface of an agricultural product; and drying the solution on the surface of the agricultural product under a forced flow of air to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a glycerophospholipid layer on the agricultural product.

(129) In another aspect, described herein is a method of preparing an agricultural product having a coating disposed thereon, the method comprising: applying a solution comprising one or more glycerophospholipids and a solvent to a surface of an agricultural product; and drying the solution on the surface of an agricultural product under a forced flow of air to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a glycerophospholipid layer on the agricultural product.

(130) In another aspect, described herein is a method of reducing the water permeability of a coating on a substrate, the method comprising: applying a solution comprising one or more glycerophospholipids and a solvent to a surface of an agricultural product; and drying the solution on the surface of an agricultural product under a forced flow of air to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a glycerophospholipid layer on the agricultural product.

(131) In another aspect, described herein is a method of reducing the gas diffusion ratio of a coating on a substrate, the comprising: applying a solution comprising one or more glycerophospholipids and a solvent to a surface of an agricultural product; and drying the solution on the surface of an agricultural product under a forced flow of air to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a glycerophospholipid layer on the agricultural product.

(132) In some embodiments, the substrate is an agricultural product, a silicon substrate, a polystyrene substrate, or a substrate comprising a polysaccharide (e.g., cellulose). For example, the substrate can be an agricultural product.

(133) In another aspect, described herein is a method of reducing the mass loss rate of an agricultural product having a coating disposed thereon, the method comprising: applying a solution comprising one or more glycerophospholipids and a solvent to a surface of an agricultural product; and drying the solution on the surface of an agricultural product under a forced flow of air to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a glycerophospholipid layer on the agricultural product.

Coating Thickness and Mass Loss Factor/Rate

(134) In some embodiments, for coatings that are formulated to prevent water loss from or oxidation of coated substrates such as produce, thicker coatings will be less permeable to water and oxygen than thinner coatings formed from the same coating agent, and should therefore result in lower mass loss rates as compared to thinner coatings. Thicker coatings can be formed by increasing the concentration of the coating agent in the solution/suspension/colloid and applying a similar volume of solution/suspension/colloid to each piece of (similarly sized) produce.

EXAMPLES

(135) The following examples describe effects of various coating agents and solutions/suspensions/colloids on various substrates, as well as characterization of some of the various coating agents and solutions/suspensions/colloids. These examples are only for illustrative purposes and are not meant to limit the scope of the present disclosure. In each of the examples below, all reagents and solvents were purchased and used without further purification unless specified.

Example 1

Effect of Coatings Formed of Glycerophospholipid on Mass Loss and Respiration Rates of Agricultural Products

(136) FIG. 1 is a graph showing mass loss factors of Hass avocados treated with various coating agents suspended in water. "Untreated" corresponds to untreated agricultural products. "MAG/FAS (95/5)" corresponds to a coating agent formed of 95% monoglyceride (thereof about 90% glycerol monostearate) and 5% sodium stearate at a concentration of 30 g/L. "Soy Lecithin" corresponds to a coating agent formed of glycerophospholipid including phosphatidylcholine, phosphatidylethanolamine, and phosphatidylinositol, where the coating agent is a lecithin derived from soy. The total concentration of glycerophospholipid was 100 g/L.

(137) All coatings were formed by bowl dipping the agricultural products in their associated solution, and allowing the agricultural products to dry under forced air flow at a temperature of 70° C. As seen in FIG. 1, the mass loss factor for the agricultural products corresponding to the glycerophospholipid coating was 1.58, the mass loss factor for the agricultural products corresponding to the MAG/FAS (95/5) coating was 1.44, and the mass loss factor for the untreated products was 1.00.

(138) As seen in FIG. 2, the respiration rate for the untreated agricultural products was higher than the respiration rate for agricultural products coated with the monoglyceride coating, which were both higher than the respiration rate for the glycerophospholipid coating.

Example 2

Structure of Glycerophospholipid Coating Measured by X-Ray Scattering

(139) Coating agents were applied to the surface of a silicon substrate, which acts as a hydrophilic surface when exposed to air. An X-ray scattering image of the applied coating was obtained to identify characteristics of the coating.

(140) A coating agent comprising phosphatidylcholine, phosphatidylethanolamine, and phosphatidylinositol (100 g/L glycerophospholipid) was applied to the surface of a polystyrene substrate. An X-ray scattering image of the applied coat was obtained and analyzed to determine characteristics of the coating based on the scattering pattern.

(141) As illustrated in FIG. 3, as determined by the scattering pattern, the coating has a hexagonal cylindrical phase (HCP) structure comprising repeating cylindrical units arranged on a hexagonal close-packed lattice on the surface of the substrate.

Example 3

Effect of Coatings Formed of Glycerophospholipid on Mass Loss and Respiration Rates of Agricultural Products Applied at Different Concentrations

(142) FIG. 4 is a graph showing mass loss factors of agricultural products treated with various coating agents suspended in water. "Untreated" corresponds to untreated agricultural products. "MAG/FAS (30 g/L)" corresponds to a coating agent formed of monoglyceride at a concentration of 30 g/L. "Lecithin" corresponds to a coating agent formed of glycerophospholipid including phosphatidylcholine, phosphatidylethanolamine, and phosphatidylinositol. The total concentration of glycerophospholipid was varied between 30-150 g/L where coatings applied at higher concentrations result in an increase in MLF.

(143) As seen in FIG. 5 and Table 2, the respiration rate for the untreated agricultural products was higher than the respiration rate for agricultural products coated with the monoglyceride coating, which were both higher than the respiration rate for the glycerophospholipid coating. Additionally, respiration rates of coatings applied at higher concentrations were lower than coatings applied at lower concentrations.

(144) TABLE-US-00002 TABLE 2 Respiration Factors. MAG/FAS Soy Soy Soy Soy (95/5) Lecithin Lecithin Lecithin Lecithin Untreated 30 g/L (30 g/L) (50 g/L) (100 g/L) (150 g/L) Respiration Factor 1.00 1.29 1.21 1.33 1.71 2.56

Example 4

Structure of Glycerophospholipid Coatings Applied at Different Concentrations Measured by X-Ray Scattering

(145) Coating agents were applied to the surface of a polystyrene substrate, which acts as a hydrophobic surface when exposed to air. An X-ray scattering image of the applied coating was obtained to identify characteristics of the coating.

(146) As illustrated in FIG. 6, as determined by the scattering pattern, coatings applied at concentrations ranging from 30-150 g/L exhibit periodic spacings of 4.9 nm. Primary peaks used for this calculation are labeled with an arrow (in black).

(147) As illustrated in FIG. 7, as determined by the scattering pattern, coatings applied at concentrations ranging from 30-150 g/L exhibit hexagonally-packed cylindrical structures (HCP) regardless of concentration comprising repeating cylindrical units arranged on a hexagonal close-packed lattice on the surface of the substrate. Peaks used to identify the characteristic HCP ratio are labeled with arrows.

(148) As illustrated in FIG. 8, as determined by the scattering pattern, coatings applied at concentrations ranging from 30-150 g/L exhibit hexagonally-packed cylindrical structures (HCP) aligned perpendicular to the substrate surface as indicated by the pronounced out-of-plane ($\perp$) scattering. Negligible scattering is observed in the in-plane ($\parallel$) direction, further suggesting alignment of the cylinders.

Example 5

Effect of Coatings Formed of Hydrogenated and Non-Hydrogenated Glycerophospholipid on Mass Loss and Respiration Rates of Agricultural Products

(149) All coatings were formed by bowl dipping the agricultural products in their associated solution, and allowing the agricultural products to dry under forced air flow at a temperature of 70° C. As seen in FIG. 9, the mass loss factor for the agricultural products corresponding to the soy-derived glycerophospholipid coating was 1.27, the mass loss factor for the agricultural products corresponding to the non-hydrogenated phosphatidylcholine (PC) was 1.44, the mass loss factor for the agricultural products corresponding to the hydrogenated phosphatidylcholine (PC) was 1.33, and the mass loss factor for the agricultural products corresponding to the MAG/FAS coating was 1.41, and the mass loss factor for the untreated products was 1.00.

Example 6

Structure of Hydrogenated and Non-Hydrogenated Glycerophospholipid Coatings Measured by X-Ray Scattering

(150) Coating agents were applied to the surface of a polystyrene substrate, which acts as a hydrophobic surface when exposed to air. An X-ray scattering image of the applied coating was obtained to identify characteristics of the coating.

(151) As illustrated in FIG. 10, coatings comprised of non-hydrogenated phosphatidyl choline and hydrogenated phosphatidylcholine exhibit periodic spacings of 3.8-4.5 nm and 6.2 nm, respectively. As illustrated in FIG. 11, as determined by the scattering pattern, the coating exhibits a lamellar structure composed of alternating bilayers on the surface of the substrate. As illustrated in FIG. 12, as determined by the scattering pattern, the coating exhibits a mixed morphology of lamella and hexagonally-packed cylinders on the surface of the substrate. Peaks used for analysis are labeled with arrows.

Example 7

Structure of Coatings Measured by X-Ray Scattering

(152) A 100 g/L solution of lyso-lecithin was prepared by blending raw material in 85° C. deionized water in a mixer until homogeneous. The solution was cooled to room temperature (20° C.) and 0.1 mL was drop casted onto a substrate, allowing time to dry at ambient conditions. FIG. 13 shows a plot of intensity vs. $q(\text{\AA}^{-1})$ from the x-ray scattering image of the lyso-lecithin coating and a 50 g/L MAG/FAS coating.

(153) While various compositions and methods have been described above, it should be understood that they have been presented by way of example only, and not limitation. Where methods and steps described above indicate certain events occurring in certain order, ordering of steps may be modified, and such modification are in accordance with the variations of the invention. Additionally, certain of the steps may be performed concurrently in a parallel process when possible, as well as performed sequentially as described above. The various implementations have been particularly shown and described, but it will be understood that various changes in form and details may be made. Accordingly, other implementations are within the scope of the following claims.

(154) Although this disclosure contains many specific embodiment details, these should not be construed as limitations on the scope of the subject matter or on the scope of what may be claimed, but rather as descriptions of features that may be specific to particular embodiments. Certain features that are described in this disclosure in the context of separate embodiments can also be implemented, in combination, in a single embodiment. Conversely, various features that are described in the context of a single embodiment can also be implemented in multiple embodiments, separately, or in any suitable sub-combination. Moreover, although previously described features may be described as acting in certain combinations and even initially claimed as such, one or more features from a claimed combination can, in some cases, be excised from the combination, and the claimed combination may be directed to a sub-combination or variation of a sub-combination.

(155) Particular embodiments of the subject matter have been described. Other embodiments, alterations, and

permutations of the described embodiments are within the scope of the following claims as will be apparent to those skilled in the art. While operations are depicted in the drawings or claims in a particular order, this should not be understood as requiring that such operations be performed in the particular order shown or in sequential order, or that all illustrated operations be performed (some operations may be considered optional), to achieve desirable results.

(156) Accordingly, the previously described example embodiments do not define or constrain this disclosure. Other changes, substitutions, and alterations are also possible without departing from the spirit and scope of this disclosure.

Claims

1. A method of reducing the ripening rate of an agricultural product, the method comprising: applying a solution comprising a coating agent to a surface of the agricultural product, wherein the coating agent comprises one or more glycerophospholipids, a temperature of the solution is between 10° C. and 80° C., and a total concentration of the one or more glycerophospholipids in the solution is between 100 g/L and 150 g/L; and drying the solution on the surface of the agricultural product under a flow of air having a temperature between 20° C. and 100° C. to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a coating on the agricultural product.
2. The method of claim 1, wherein the one or more glycerophospholipids comprise one or more of phosphatidylcholine, phosphatidylethanolamine, phosphatidylinositol, phosphatidylserine, and phosphatidic acid.
3. The method of claim 1, wherein the one or more glycerophospholipids comprise one or more compounds of Formula I: `##STR00029##` wherein: R^{sup.1} is —H or one of the following fragments: `##STR00030##` and R^{sup.2} and R^{sup.3} are each independently, at each occurrence, —H or a fragment represented by Formula II: `##STR00031##` wherein: R^{sup.4}, R^{sup.5}, R^{sup.8}, R^{sup.9}, R^{sup.12}, R^{sup.13}, R^{sup.14}, R^{sup.15} and R^{sup.16} are each independently, at each occurrence, —H, —OH, —OR^{sup.17} or C_{sub.1}-C_{sub.6} alkyl; R^{sup.6}, R^{sup.7}, R^{sup.10}, and R^{sup.11} are each independently, at each occurrence, —H, —OR^{sup.17}, or C_{sub.1}-C_{sub.6} alkyl; and/or R^{sup.4} and R^{sup.5} can combine with the carbon atoms to which they are attached to form C=O; and/or R^{sup.8} and R^{sup.9} can combine with the carbon atoms to which they are attached to form C=O; and/or R^{sup.12} and R^{sup.13} can combine with the carbon atoms to which they are attached to form C=O; and R^{sup.17} is at each occurrence a C_{sub.1}-C_{sub.6} alkyl, the symbol  represents a single bond or a cis or trans double bond; n is 0, 1, 2, 3, 4, 5, 6, 7 or 8; m is 0, 1, 2 or 3; q is 0, 1, 2, 3, 4 or 5; and r is 0, 1, 2, 3, 4, 5, 6, 7 or 8.
4. The method of claim 3, wherein the fragment represented by Formula II is one of: `##STR00032##` `##STR00033##` `##STR00034##` `##STR00035##`
5. The method of claim 1, wherein the one or more glycerophospholipids comprise phosphatidylcholine, phosphatidylethanolamine, and phosphatidylinositol.
6. The method of claim 5, wherein the one or more glycerophospholipids comprise 20 wt % to 40 wt % phosphatidylcholine, 20 wt % to 40 wt % phosphatidylethanolamine, and 20 wt % to 40 wt % phosphatidylinositol.
7. The method of claim 5, wherein the one or more glycerophospholipids further comprise phosphatidylserine.
8. The method of claim 1, wherein the solution further comprises a phytosterol.
9. The method of claim 8, wherein a weight ratio of the phytosterol to a total amount of the one or more glycerophospholipids is less than 0.05.
10. The method of claim 1, wherein the solution is an aqueous solution.
11. The method of claim 1, wherein a temperature of the air is between 50° C. and 100° C.
12. The method of claim 1, wherein the multiplicity of glycerophospholipid bilayers comprise one or more open bilayers.
13. The method of claim 12, wherein the one or more open bilayers are lamellar.
14. The method of claim 1, wherein the multiplicity of glycerophospholipid bilayers comprise one or more closed bilayers.
15. The method of claim 14, wherein one or more of the closed bilayers are cylindrical.
16. The method of claim 14, wherein one or more of the closed bilayers are spherical.
17. The method of claim 1, wherein a thickness of the coating is less than 2 microns.
18. A method of preparing an agricultural product having a coating disposed thereon, the method comprising:

applying a solution comprising a coating agent to a surface of the agricultural product, wherein the coating agent comprises one or more glycerophospholipids, a temperature of the solution is between 10° C. and 80° C., and a total concentration of the one or more glycerophospholipids in the solution is between 100 g/L and 150 g/L; and drying the solution on the surface of the agricultural product under a flow of air having a temperature between 20° C. and 100° C. to promote self-assembly of a multiplicity of glycerophospholipid bilayers on the surface of the agricultural product, thereby forming a coating on the agricultural product.

19. A coated agricultural product comprising: an agricultural product; and a coating on the surface of the agricultural product, wherein the coating comprises one or more glycerophospholipids, wherein the coating has a hexagonal cylindrical phase structure comprising repeating cylindrical units arranged on a hexagonal close-packed lattice on the surface of the structure, and the coating is applied to the surface of the agricultural product as a solution comprising one or more glycerophospholipids in a total concentration between 100 g/L and 150 g/L.
