

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12402508
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Kim; Younggu et al.

Display apparatus including a low refractive index layer

Abstract

A display apparatus includes a first through a third light-emitting devices, each including a first-color emission layer and being over a substrate; a second-color quantum dot layer over the second light-emitting device; a third-color quantum dot layer over the third light-emitting device; and a low refractive index layer over the second-color quantum dot layer and the third-color quantum dot layer to correspond to the first through third light-emitting devices, and including a matrix part and a plurality of particles in the matrix part, wherein a first portion of the matrix part close to the first through third light-emitting devices includes fluorine.

Inventors: Kim; Younggu (Yongin-si, KR), Park; Jiyun (Yongin-si, KR), Seo; Bongsung (Yongin-si, KR), Son; Jongho (Yongin-si, KR), Lyu; Jaejin (Yongin-si, KR), Lee; Yeonhee (Yongin-si, KR), Jeon; Baekkyun (Yongin-si, KR), Tak; Kyungseon (Yongin-si, KR)

Applicant: SAMSUNG DISPLAY CO., LTD. (Yongin-si, KR)

Family ID: 1000008779173

Assignee: Samsung Display Co., Ltd. (Yongin-si, KR)

Appl. No.: 18/522217

Filed: November 28, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20240114742 A1	Apr. 04, 2024

Foreign Application Priority Data

KR	10-2020-0101399	Aug. 12, 2020
----	-----------------	---------------

Related U.S. Application Data

division parent-doc US 17224002 20210406 US 11839129 child-doc US 18522217

Publication Classification

Int. Cl.: H10K59/38 (20230101); H10K59/12 (20230101); H10K59/80 (20230101)

U.S. Cl.:

CPC H10K59/38 (20230201); H10K59/12 (20230201); H10K59/879 (20230201); H10K59/877 (20230201)

Field of Classification Search

CPC: H10K (50/854); H10K (2102/331); H10K (2101/80)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8877104	12/2013	Iwata et al.	N/A	N/A
10371875	12/2018	Kim et al.	N/A	N/A
11839129	12/2022	Kim	N/A	H10K 59/38
2008/0311407	12/2007	Kim	428/480	G02B 1/111
2014/0312339	12/2013	Fujita	N/A	N/A
2015/0144900	12/2014	Lee	257/40	H10K 50/82
2018/0081101	12/2017	Kobori	N/A	G02B 5/305
2018/0156951	12/2017	Baek	N/A	G02F 1/133617
2018/0305472	12/2017	Kobori	N/A	C08K 5/11
2020/0012016	12/2019	Heo	N/A	H10K 50/86
2020/0018872	12/2019	Fujii et al.	N/A	N/A
2020/0081173	12/2019	Tak	N/A	G02F 1/133617
2020/0081292	12/2019	Park et al.	N/A	N/A
2020/0168668	12/2019	Kim et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
108153036	12/2017	CN	N/A
2004-345278	12/2003	JP	N/A
5846243	12/2015	JP	N/A
10-1202089	12/2011	KR	N/A
10-1725585	12/2016	KR	N/A
10-2017-0049383	12/2016	KR	N/A
10-1769093	12/2016	KR	N/A
10-2018-0064616	12/2017	KR	N/A

10-2032316	12/2018	KR	N/A
10-2020-0030147	12/2019	KR	N/A
10-2020-0030156	12/2019	KR	N/A
10-2020-0063964	12/2019	KR	N/A

OTHER PUBLICATIONS

Office Action in corresponding Chinese Patent Application No. 202110835828.9, issued Jun. 28, 2025. cited by applicant

Primary Examiner: Ojeh; Nduka E

Attorney, Agent or Firm: Womble Bond Dickinson (US) LLP

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a divisional of U.S. patent application Ser. No. 17/224,002, filed Apr. 6, 2021, which claims priority to and the benefit of Korean Patent Application No. 10-2020-0101399, filed Aug. 12, 2020, the entire content of both of which is incorporated herein by reference.

BACKGROUND

1. Field

(1) One or more embodiments relate to a display apparatus, and more particularly, to a display apparatus having high luminous efficiency and a simplified structure.

2. Description of Related Art

(2) A display apparatus includes a plurality of pixels. In the case of a full-color display apparatus, the plurality of pixels may emit light of different colors. To this end, at least some pixels of the display apparatus may include a color conversion unit. Accordingly, light of a first color generated by a light emitter of some pixels is converted into light of a second color while passing through a corresponding color conversion unit and is transmitted to the outside.

SUMMARY

(3) A display apparatus according to the related art has a problem in that a structure thereof becomes complicated to improve the luminous efficiency.

(4) An aspect of one or more embodiments of the present disclosure are directed towards a display apparatus having high luminous efficiency and a simplified structure. However, the disclosed embodiments and aspects are examples, and the present disclosure is not limited thereto.

(5) Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

(6) According to one or more embodiments, a display apparatus includes a substrate, a first light-emitting device, a second light-emitting device, and a third light-emitting device each including a first-color emission layer and being over the substrate, a second-color quantum dot layer over the second light-emitting device, a third-color quantum dot layer over the third light-emitting device, a low refractive index layer over the second-color quantum dot layer and the third-color quantum dot layer to correspond to the first through third light-emitting devices, and including a matrix part and a plurality of particles in the matrix part, wherein a first portion of the matrix part away from the first through third light-emitting devices includes fluorine, a first-color color filter layer over the low refractive index layer to correspond to the first light-emitting device, a second-color color filter layer over the low refractive index layer to correspond to the second light-emitting device, and a third-color color filter layer over the low refractive index layer to correspond to the third light-

emitting device.

(7) The display apparatus may further include a light-transmitting layer over the first light-emitting device, wherein the low refractive index layer is over the light-transmitting layer.

(8) The first portion of the matrix part may be greater in fluorine content per unit volume than a second portion of the matrix part, the second portion being closer to the first through third light-emitting devices than the first portion of the matrix part is to the first through third light-emitting devices.

(9) The first portion of the matrix part may be greater in fluorine content per unit volume than a second portion of the matrix part close to the first through third light-emitting devices.

(10) The farther away from the first through third light-emitting devices, the greater a fluorine content per unit volume in the matrix part may be.

(11) A second portion of the matrix part closer to the first through third light-emitting devices than the first portion of the matrix part may be to the first through third light-emitting devices may not include fluorine.

(12) A first portion of the low refractive index layer may be less in number of the plurality of particles per unit volume than a second portion of the low refractive index layer closer to the first through third light-emitting devices than the first portion of the low refractive index layer may be to the first through third light-emitting devices.

(13) A first portion of the low refractive index layer away from the first through third light-emitting devices may be less in number of the plurality of particles per unit volume than a second portion of the low refractive index layer close to the first through third light-emitting devices.

(14) A first portion of the low refractive index layer far from the first through third light-emitting devices may not include the plurality of particles.

(15) The display apparatus may further include a capping layer between the low refractive index layer and the second-color and third-color quantum dot layers to correspond to the first through third light-emitting devices.

(16) The matrix part may be integrally formed as a single body from a bottom surface of the low refractive index layer close to the first through third light-emitting devices to a top surface of the low refractive index layer away from the first through third light-emitting devices.

(17) According to one or more embodiments, a display apparatus includes a substrate, a first light-emitting device, a second light-emitting device, and a third light-emitting device, each including a first-color emission layer and being over the substrate, a second-color quantum dot layer over the second light-emitting device, a third-color quantum dot layer over the third light-emitting device, a low refractive index layer over the second-color quantum dot layer and the third-color quantum dot layer to correspond to the first through third light-emitting devices, and including a matrix part and a plurality of particles in the matrix part, wherein a first portion of the matrix part close to the first through third light-emitting devices includes fluorine, a first-color color filter layer over the low refractive index layer to correspond to the first light-emitting device, a second-color color filter layer over the low refractive index layer to correspond to the second light-emitting device, and a third-color color filter layer over the low refractive index layer to correspond to the third light-emitting device.

(18) The display apparatus may further include a light-transmitting layer over the first light-emitting device, wherein the low refractive index layer is over the light-transmitting layer.

(19) The first portion of the matrix part may be greater in fluorine content per unit volume than a second portion of the matrix part farther from the first through third light-emitting devices than the first portion of the matrix part may be to the first through third light-emitting devices.

(20) The first portion of the matrix part may be greater in fluorine content per unit volume than a second portion of the matrix part away from the first through third light-emitting devices.

(21) The closer to the first through third light-emitting devices, the greater a fluorine content per unit volume in the matrix part may be.

- (22) A second portion of the matrix part farther from the first through third light-emitting devices than the first portion of the matrix part may be to the first through third light-emitting devices may not include fluorine.
- (23) A first portion of the low refractive index layer may be less in number of the plurality of particles per unit volume than a second portion of the low refractive index layer farther from the first through third light-emitting devices than the first portion of the low refractive index layer may be to the first through third light-emitting devices.
- (24) A first portion of the low refractive index layer close to the first through third light-emitting devices may be less in number of the plurality of particles per unit volume than a second portion of the low refractive index layer away from the first through third light-emitting devices.
- (25) A first portion of the low refractive index layer close to the first through third light-emitting devices may not include the plurality of particles.
- (26) The display apparatus may further include a capping layer between the low refractive index layer and the first-color through third-color color filter layers to correspond to the first through third light-emitting devices.
- (27) The matrix part may be integrally formed as a single body from a bottom surface of the low refractive index layer close to the first through third light-emitting devices to a top surface of the low refractive index layer away from the first through third light-emitting devices.
- (28) Other aspects and features of the present disclosure will become more apparent from the drawings, the claims, and the detailed description.
-

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) The above and other aspects and features of embodiments of the present disclosure will be more apparent from the following description taken in conjunction with the accompanying drawings, in which:
- (2) FIG. 1 is a cross-sectional view illustrating a portion of a display apparatus according to an embodiment;
- (3) FIGS. 2 and 3 are each a cross-sectional view illustrating a process of manufacturing the display apparatus of FIG. 1, according to an embodiment;
- (4) FIG. 4 is a cross-sectional view illustrating a portion of a display apparatus according to another embodiment;
- (5) FIG. 5 is a cross-sectional view illustrating a portion of a display apparatus according to another embodiment;
- (6) FIGS. 6 through 9 are each a cross-sectional view illustrating a process of manufacturing the display apparatus of FIG. 5, according to an embodiment;
- (7) FIG. 10 is a cross-sectional view illustrating a portion of a display apparatus according to another embodiment; and
- (8) FIG. 11 is a cross-sectional view illustrating a portion of a display apparatus according to another embodiment.

DETAILED DESCRIPTION

(9) Reference will now be made in more detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the embodiments of the present disclosure may have different suitable forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, some example embodiments are described below, by referring to the drawings, to explain aspects and features of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Throughout the disclosure, the

expression “at least one of a, b or c” indicates only a, only b, only c, both a and b, both a and c, both b and c, all of a, b, and c, or variations thereof. Also, “at least one selected from among a, b, and c” indicates only a, only b, only c, both a and b, both a and c, both b and c, all of a, b, and c, or variations thereof.

(10) As the present disclosure allows for various suitable changes and numerous embodiments, certain embodiments will be illustrated in the drawings and described in the detailed description. Aspects and features of the present disclosure, and methods for achieving them, will be clarified with reference to embodiments described below in more detail with reference to the drawings. However, the present disclosure is not limited to the following embodiments and may be embodied in various suitable forms.

(11) Hereinafter, embodiments will be described with reference to the accompanying drawings, wherein like elements are denoted by like reference numerals throughout and a repeated description thereof may not be provided.

(12) It will be understood that when a component, such as a layer, a film, a region, or a plate, is referred to as being “on” another component, the component may be directly on the other component or one or more intervening components may be present therebetween. Also, sizes of elements in the drawings may be exaggerated or contracted for convenience of explanation. For example, because sizes and thicknesses of elements in the drawings may be exaggerated or contracted for convenience of explanation, the present disclosure is not limited thereto.

(13) Also, any numerical range recited herein is intended to include all sub-ranges of the same numerical precision subsumed within the recited range. For example, a range of “1.0 to 10.0” is intended to include all subranges between (and including) the recited minimum value of 1.0 and the recited maximum value of 10.0, that is, having a minimum value equal to or greater than 1.0 and a maximum value equal to or less than 10.0, such as, for example, 2.4 to 7.6. Any maximum numerical limitation recited herein is intended to include all lower numerical limitations subsumed therein and any minimum numerical limitation recited in this specification is intended to include all higher numerical limitations subsumed therein. Accordingly, Applicant reserves the right to amend this specification, including the claims, to expressly recite any sub-range subsumed within the ranges expressly recited herein.

(14) In the following examples, an X-axis, a Y-axis, and a Z-axis are not limited to three axes of a rectangular coordinate system, and may be interpreted in a broader sense. For example, the X-axis, the Y-axis, and the Z-axis may be perpendicular to one another or may represent different directions that are not perpendicular to one another.

(15) FIG. 1 is a cross-sectional view illustrating a portion of a display apparatus according to an embodiment. As shown in FIG. 1, the display apparatus according to the present embodiment includes a first pixel PX1, a second pixel PX2, and a third pixel PX3. However, this is merely an example, and the display apparatus may include more pixels. Although the first pixel PX1 through the third pixel PX3 are adjacent to one another in FIG. 1, the present disclosure is not limited thereto. For example, elements such as wirings may be located among the first pixel PX1 through the third pixel PX3. Accordingly, for example, the first pixel PX1 and the second pixel PX2 may not be located adjacent to each other. Also, cross-sections of the first pixel PX1 through the third pixel PX3 in FIG. 1 may not be cross-sections in the same direction.

(16) The display apparatus according to the present embodiment includes a substrate 100. The substrate 100 may include (e.g., be) glass, a metal, and/or a polymer resin. When the substrate 100 is flexible and/or bendable, the substrate 100 may include (e.g., be) a polymer resin such as polyethersulfone, polyacrylate, polyetherimide, polyethylene naphthalate, polyethylene terephthalate, polyphenylene sulfide, polyarylate, polyimide, polycarbonate, and/or cellulose acetate propionate. Various suitable modifications may be made. For example, the substrate 100 may have a multi-layer structure including two layers, each including (e.g., being) a polymer resin, and a barrier layer including (e.g., being) an inorganic material such as silicon oxide, silicon

nitride, and/or silicon oxynitride and disposed between the two layers.

(17) A first pixel electrode **311**, a second pixel electrode **321**, and a third pixel electrode **331** are disposed over the substrate **100**. In some embodiments, a plurality of display devices are disposed over the substrate **100**. First through third thin-film transistors **210**, **220**, and **230** electrically coupled (e.g., connected) to the display devices may also be disposed over the substrate **100**. In FIG. **1**, organic light-emitting devices are disposed as the display devices over the substrate **100**. When the organic light-emitting devices are electrically coupled (e.g., connected) to the first through third thin-film transistors **210**, **220**, and **230**, the first through third pixel electrodes **311**, **321**, and **331** may be electrically coupled (e.g., connected) to the first through third thin-film transistors **210**, **220**, and **230**.

(18) For reference, in FIG. **1**, the first thin-film transistor **210** is located in the first pixel PX1, the second thin-film transistor **220** is located in the second pixel PX2, and the third thin-film transistor **230** is located in the third pixel PX3. Each of the first through third thin-film transistors **210**, **220**, and **230** is electrically coupled (e.g., connected) to a pixel electrode of a display device located in the corresponding pixel. For convenience of explanation, the first thin-film transistor **210** and a display device coupled (e.g., connected) to the first thin-film transistor **210** will be described, and the description may apply to the second thin-film transistor **220** and the third thin-film transistor **230** and display devices coupled (e.g., connected) to the second thin-film transistor **220** and the third thin-film transistor **230**. Thus, a description of a second semiconductor layer **221**, a second gate electrode **223**, a second source electrode **225a**, and a second drain electrode **225b** of the second thin-film transistor **220**, and the second pixel electrode **321** may not be provided. Likewise, a description of a third semiconductor layer **231**, a third gate electrode **233**, a third source electrode **235a**, and a third drain electrode **235b** of the third thin-film transistor **230**, and the third pixel electrode **331** may not be provided.

(19) The first thin-film transistor **210** may include a first semiconductor layer **211** including (e.g., being) amorphous silicon, polycrystalline silicon, an organic semiconductor material, and/or an oxide semiconductor material, a first gate electrode **213**, a first source electrode **215a**, and a first drain electrode **215b**. The first gate electrode **213** may include (e.g., be) any of various suitable conductive materials and may have any of various suitable layer structures. For example, the first gate electrode **213** may include (e.g., be) a molybdenum (Mo) layer and/or an aluminum (Al) layer. In some embodiments, the first gate electrode **213** may include (e.g., be) a TiNx layer, an Al layer, and/or a titanium (Ti) layer. Each of the first source electrode **215a** and the first drain electrode **215b** may also have any of various suitable conductive materials and may have any of various suitable layer structures. For example, each of the first source electrode **215a** and the first drain electrode **215b** may include (e.g., be) a Ti layer, an Al layer, and/or a copper (Cu) layer. The first semiconductor layer **211** may have a source region and/or a drain region, and the first source electrode **215a** or the first drain electrode **215b** as shown in FIG. **1** may be a wiring coupled (e.g., connected) to the source region or the drain region of the first semiconductor layer **211**. For example, the first semiconductor layer **211** may have a source region, a drain region, and a channel region between the source region and the drain region; the first source electrode **215a** may be coupled (e.g., connected) to the source region; and the first drain electrode **215b** may be coupled (e.g., connected) to the drain region. In some embodiments, the first gate electrode **213** may overlap the channel region of the first semiconductor layer **211**. This may apply to the following embodiments and modifications thereof.

(20) In order to ensure insulation between the first semiconductor layer **211** and the first gate electrode **213**, a gate insulating film **121** including (e.g., being) an inorganic material such as silicon oxide, silicon nitride, and/or silicon oxynitride may be disposed between the first semiconductor layer **211** and the first gate electrode **213**. A first interlayer insulating film **131** including (e.g., being) an inorganic material such as silicon oxide, silicon nitride, and/or silicon oxynitride may be disposed over the first gate electrode **213**, and the first source electrode **215a**

and the first drain electrode **215b** may be disposed over the first interlayer insulating film **131**. As such, an insulating film including (e.g., being) an inorganic material may be formed by utilizing chemical vapor deposition (CVD) and/or atomic layer deposition (ALD). This may apply to the following embodiments and modifications thereof.

(21) A buffer layer **110** including (e.g., being) an inorganic material such as silicon oxide, silicon nitride, and/or silicon oxynitride may be disposed between the substrate **100** and the first thin-film transistor **210** having the above structure. The buffer layer **110** may planarize a top surface of the substrate **100**, or may prevent, reduce, or minimize impurities from the substrate **100** and/or the like from penetrating into the first semiconductor layer **211** of the first thin-film transistor **210**.

(22) A planarization layer **140** may be disposed over the first thin-film transistor **210**. For example, when an organic light-emitting device is disposed over the first thin-film transistor **210** as shown in FIG. **1**, the planarization **140** may substantially planarize a top surface of a protective film covering the first thin-film transistor **210**. The planarization layer **140** may include (e.g., be) an organic material such as acryl, benzocyclobutene (BCB), and/or hexamethyldisiloxane (HMDSO).

Although the planarization layer **140** has a single-layer structure in FIG. **1**, various suitable modifications may be made. For example, the planarization layer **140** may have a multi-layer structure.

(23) A display device may be disposed over the planarization layer **140** of the substrate **100**. An organic light-emitting device as shown in FIG. **1** may be utilized as the display device. In the first pixel PX1, the organic light-emitting device may include, for example, the first pixel electrode **311**, a counter electrode **305**, and an intermediate layer **303** disposed between the first pixel electrode **311** and the counter electrode **305** and including an emission layer. The first pixel electrode **311** is electrically coupled (e.g., connected) to the first thin-film transistor **210** by contacting one of the first source electrode **215a** and the first drain electrode **215b** through an opening portion (e.g., a contact hole) formed in the planarization layer **140** as shown in FIG. **1**. The second pixel PX2 includes the second pixel electrode **321**, and the third pixel PX3 includes the third pixel electrode **331**. Each of the first through third pixel electrodes **311**, **321**, and **331** may include a light-transmitting conductive layer formed of a light-transmitting conductive oxide such as indium tin oxide (ITO), In.sub.2O.sub.3, and/or indium zinc oxide (IZO), and a reflective layer formed of a metal such as aluminum (Al) and/or silver (Ag). For example, each of the first through third pixel electrodes **311**, **321**, and **331** may have a 3-layer structure including ITO/Ag/ITO.

(24) The intermediate layer **303** including the emission layer may be integrally formed over the first through third pixel electrodes **311**, **321**, and **331**, and the counter electrode **305** on the intermediate layer **303** may also be integrally formed over the first through third pixel electrodes **311**, **321**, and **331**. The counter electrode **305** may include a light-transmitting conductive layer formed of ITO, In.sub.2O.sub.3, and/or IZO, and may include a semi-transmissive film including (e.g., being) a metal such as silver (Ag), magnesium (Mg), and/or ytterbium (Yb). For example, the counter electrode **305** may be a semi-transmissive film including (e.g., being) MgAg and/or AgYb.

(25) A pixel-defining layer **150** may be disposed over the planarization layer **140**. The pixel-defining layer **150** has an opening corresponding to each pixel, for example, an opening through which at least a central portion of each of the first through third pixel electrodes **311**, **321**, and **331** is exposed, to define the pixel. For example, the pixel-defining layer **150** may cover a portion (e.g., an edge) of the first pixel electrode **311** and may have an opening that exposes another portion (e.g., a central portion) of an upper surface of the first pixel electrode **311**. Also, as shown in FIG. **1**, the pixel-defining layer **150** increases a distance between the counter electrode **305** and an edge of each of the first through third pixel electrodes **311**, **321**, and **331**, to prevent an arc and/or the like from occurring at the edge of each of the first through third pixel electrodes **311**, **321**, and **331**, or to suppress the formation of an arc and/or the like. The pixel-defining layer **150** may include (e.g., be) an organic material such as polyimide and/or hexamethyldisiloxane (HMDSO).

(26) The intermediate layer **303** may include (e.g., be) a low molecular weight material or a high

molecular weight material. When the intermediate layer **303** has a low molecular weight material, the intermediate layer **303** may have a single or multi-layer structure in which a hole injection layer (HIL), a hole transport layer (HTL), an emission layer (EML), an electron transport layer (ETL), and an electron injection layer (EIL) are stacked, and may be formed by utilizing vacuum deposition. In some embodiments, the intermediate layer **303** may include the EML and one or more of the HIL, the HTL, the ETL, and the EIL. When the intermediate layer **303** includes (e.g., is) a high molecular weight material, the intermediate layer **303** may have a structure including an HTL and an EML. In this case, the HTL may include (e.g., be) poly(3,4-ethylenedioxythiophene) (PEDOT), and the EML may include (e.g., be) a polymer material such as a polyphenylene vinylene (PPV)-based material and/or a polyfluorene-based material. The intermediate layer **303** may be formed by utilizing screen printing, inkjet printing, deposition, and/or laser-induced thermal imaging (LITI). However, the intermediate layer **303** is not limited thereto, and may have any of various suitable other structures.

(27) Although the intermediate layer **303** may include a layer that is integrally formed over the first through third pixel electrodes **311**, **321**, and **331** as described above, the intermediate layer **303** may include a layer that is patterned to correspond to each of the first through third pixel electrodes **311**, **321**, and **331**. In some embodiments, the intermediate layer **303** includes a first-color emission layer. The first-color emission layer may be integrally formed over the first through third pixel electrodes **311**, **321**, and **331**, or may be patterned to correspond to each of the first through third pixel electrodes **311**, **321**, and **331**. The first-color emission layer may emit light of a first wavelength band, for example, light having a wavelength of about 450 nm to about 495 nm.

(28) The counter electrode **305** is disposed over the intermediate layer **303** to correspond to the first through third pixel electrodes **311**, **321**, and **331**. The counter electrode **305** may be integrally formed in a plurality of organic light-emitting devices.

(29) Because each organic light-emitting device may be easily damaged by external moisture, oxygen, and/or the like, an encapsulation layer **500** may cover and protect the organic light-emitting device. The encapsulation layer **500** may include a first inorganic encapsulation layer **510**, an organic encapsulation layer **520**, and a second inorganic encapsulation layer **530**. The first inorganic encapsulation layer **510** and the second inorganic encapsulation layer **530**, which may each include (e.g., be) an inorganic material such as silicon oxide, silicon nitride, and/or silicon oxynitride, may contact each other outside the organic encapsulation layer **520**. For example, each of the first and second inorganic encapsulation layers **510** and **530** may extend beyond the organic encapsulation layer **520** in a plan view and come into contact to partially or entirely encapsulate the organic encapsulation layer **520**. The organic encapsulation layer **520** may include (e.g., be), for example, polydimethylsiloxane and/or polyacrylate.

(30) A second-color quantum dot layer **425** is disposed over a second light-emitting device located in the second pixel PX2. For example, the second-color quantum dot layer **425** is disposed over the second pixel electrode **321** of the second light-emitting device located in the second pixel PX2. Accordingly, when viewed in a direction (Z-axis direction) perpendicular to the substrate **100** (e.g., when viewed in a plan view), the second-color quantum dot layer **425** overlaps the second pixel electrode **321**. The second-color quantum dot layer **425** may convert light of the first wavelength band generated by the intermediate layer **303** on the second pixel electrode **321** into light of a second wavelength band. For example, when light having a wavelength of about 450 nm to about 495 nm is generated by the intermediate layer **303** on the second pixel electrode **321**, the second-color quantum dot layer **425** may convert the light into light having a wavelength of about 495 nm to about 570 nm. Accordingly, in the second pixel PX2, light having a wavelength of about 495 nm to about 570 nm is emitted to the outside.

(31) A third-color quantum dot layer **435** is disposed over a third light-emitting device located in the third pixel PX3. For example, the third-color quantum dot layer **435** is disposed over the third pixel electrode **331** of the third light-emitting device located in the third pixel PX3. Accordingly,

when viewed in the direction (Z-axis direction) perpendicular to the substrate **100** (e.g., when viewed in the plan view), the third-color quantum dot layer **435** overlaps the third pixel electrode **331**. The third-color quantum dot layer **435** may convert light of the first wavelength band generated by the intermediate layer **303** on the third pixel electrode **331** into light of a third wavelength band. For example, when light having a wavelength of about 450 nm to about 495 nm is generated by the intermediate layer **303** on the third pixel electrode **331**, the third-color quantum dot layer **435** may convert the light into light having a wavelength of about 630 nm to about 780 nm. Accordingly, in the third pixel PX3, light having a wavelength of about 630 nm to about 780 nm is emitted to the outside.

(32) Each of the second-color quantum dot layer **425** and the third-color quantum dot layer **435** may have a structure in which quantum dots are dispersed in a resin. In some embodiments and modifications thereof, quantum dots may refer to semiconductor compound crystals, and may include (e.g., be) any suitable material capable of emitting light having various suitable wavelengths according to sizes of crystals. A diameter of each of the quantum dots may range, for example, from about 1 nm to about 10 nm.

(33) Quantum dots may be synthesized by utilizing a wet chemical process, metal organic chemical deposition (MOCVD), molecular beam epitaxy (MBE), and/or the like. A wet chemical process is a method of mixing an organic solvent with a precursor material and then growing quantum dot crystals. In a wet chemical process, when crystals are grown, because an organic solvent naturally functions as a dispersant coordinated on quantum dot crystal surfaces and controls the growth of the crystals, the wet chemical process is easier than a vapor deposition method such as organic metal chemical vapor deposition (MOCVD) or molecular beam epitaxy (MBE). Also, the wet chemical process is inexpensive and may control the growth of quantum dot particles.

(34) Such quantum dots may include (e.g., be) a group III-VI semiconductor compound, a group II-VI semiconductor compound, a group III-V semiconductor compound, a group III-VI semiconductor compound, a group I-III-VI semiconductor compound, a group IV-VI semiconductor compound, a group IV element or compound, or any combination thereof.

(35) Examples of the group III-VI semiconductor compound may include a binary compound such as In.sub.2S.sub.3, a ternary compound such as AgInS, AgInS.sub.2, CuInS, and/or CuInS.sub.2, or any combination thereof.

(36) Examples of the group II-VI semiconductor compound include a binary compound such as CdS, CdSe, CdTe, ZnS, ZnSe, ZnTe, ZnO, HgS, HgSe, HgTe, MgSe, and/or MgS, a ternary compound such as CdSeS, CdSeTe, CdSTe, ZnSeS, ZnSeTe, ZnSTe, HgSeS, HgSeTe, HgSTe, CdZnS, CdZnSe, CdZnTe, CdHgS, CdHgSe, CdHgTe, HgZnS, HgZnSe, HgZnTe, MgZnSe, and/or MgZnS, a quaternary compound such as CdZnSeS, CdZnSeTe, CdZnSTe, CdHgSeS, CdHgSeTe, CdHgSTe, HgZnSeS, HgZnSeTe, and/or HgZnSTe, or any combination thereof.

(37) Examples of the group III-V semiconductor compound include a binary compound such as GaN, GaP, GaAs, GaSb, AlN, AlP, AlAs, AlSb, InN, InP, InAs, and/or InSb, a ternary compound such as GaNP, GaNAs, GaNSb, GaPAs, GaPSb, AlNP, AlNAs, AlNSb, AlPAs, AlPSb, InGaP, InNP, InAlP, InNAs, InNSb, InPAs, InPSb, and/or GaAlNP, a quaternary compound such as InAlNAs, InAlNSb, InAlPAs, and/or InAlPSb, or any combination thereof. The group III-V semiconductor compound may further include (e.g., be) a group II element. Examples of the group III-V semiconductor compound further including the group II element may include InZnP, InGaZnP, and/or InAlZnP.

(38) Examples of the III-VI group semiconductor compound may include a binary compound such as GaS, GaSe, Ga.sub.2Se.sub.3, GaTe, InS, InSe, In.sub.2Se.sub.3, and/or InTe, a ternary compound such as InGaS.sub.3 and/or InGaSe.sub.3, or any combination thereof.

(39) Examples of the group I-III-VI semiconductor compound may include a ternary compound such as AgInS, AgInS.sub.2, CuInS, CuInS.sub.2, CuGaO.sub.2, AgGaO.sub.2, and/or AgAlO.sub.2, or any combination thereof.

(40) Examples of the group IV-VI semiconductor compound may include a binary compound such as SnS, SnSe, SnTe, PbS, PbSe, and/or PbTe, a ternary compound such as SnSeS, SnSeTe, SnSTe, PbSeS, PbSeTe, PbSTe, SnPbS, SnPbSe, and/or SnPbTe, a quaternary compound such as SnPbSSe, SnPbSeTe, and/or SnPbSTe, or any combination thereof.

(41) Examples of the group IV element or compound may include a single-element compound such as Si and/or Ge, a binary compound such as SiC and/or SiGe, or any combination thereof.

(42) Elements included in a multi-element compound such as a binary compound, a ternary compound, and/or a quaternary compound may exist in particles at a uniform concentration or a non-uniform concentration.

(43) A quantum dot may have a core-shell structure or a single structure having a uniform element concentration in the quantum dot. For example, a material included in (e.g., composing) a core and a material included in (e.g., composing) a shell may be different from each other. The shell of the quantum dot may serve as a protective layer for maintaining semiconductor characteristics by preventing, suppressing, or reducing the occurrence of, chemical degeneration of the core and/or a charging layer for providing electrophoretic characteristics to the quantum dot. The shell may have a single or multi-layer structure. An interface between the core and the shell may have a concentration gradient in which an element concentration in the shell gradually decreases toward the center.

(44) Examples of the shell of the quantum dot may include (e.g., be) a metallic or non-metallic oxide, a semiconductor compound, or a combination thereof. Examples of the metallic or non-metallic oxide may include a binary compound such as SiO_2 , Al_2O_3 , TiO_2 , ZnO, MnO, Mn_2O_3 , Mn_3O_4 , CuO, FeO, Fe_2O_3 , Fe_3O_4 , CoO, Co_3O_4 , and/or NiO, a ternary compound such as MgAl_2O_4 , CoFe_2O_4 , NiFe_2O_4 , and/or CoMnO_4 , or any combination thereof. Examples of the semiconductor compound may include, as described above, a group III-VI semiconductor compound, a group II-VI semiconductor compound, a group III-V semiconductor compound, a group III-VI semiconductor compound, a group I-III-VI semiconductor compound, a group IV-VI semiconductor compound, or any combination thereof. Examples of the semiconductor compound may include CdS, CdSe, CdTe, ZnS, ZnSe, ZnTe, ZnSeS, ZnTeS, GaAs, GaP, GaSb, HgS, HgSe, HgTe, InAs, InP, InGaP, InSb, AlAs, AlP, AlSb, or any combination thereof.

(45) A quantum dot may have a full width at half maximum (FWHM) of an emission wavelength spectrum of about 45 nm or less. In some embodiments, the FWHM may be about 40 nm or less. In some embodiments, the FWHM may be about 30 nm or less. When the FWHM is in this range, color purity or color reproducibility may be improved. Also, because light emitted through the quantum dot is emitted in all directions, an optical viewing angle may be improved.

(46) A quantum dot may be a spherical, pyramid, multi-arm, or cubic-shaped nano particle, nanotube, nano-wire, nano-fiber, or nano-plate particle.

(47) Because an energy band gap (e.g., a wavelength band) may be adjusted by adjusting a size of a quantum dot, light of various suitable wavelength bands may be obtained through a quantum dot emission layer. Accordingly, a light-emitting device for emitting light having various suitable wavelengths may be realized by utilizing quantum dots having different sizes. In more detail, sizes of quantum dots may be selected or set to emit red light, green light, and/or blue light. Also, sizes of quantum dots may be selected or set to combine light of various colors and emit white light.

(48) Each of the second-color quantum dot layer **425** and the third-color quantum dot layer **435** may include a scatterer. Any suitable resin included in each of the second-color quantum dot layer **425** and the third-color quantum dot layer **435** may be utilized as long as it has suitable dispersion characteristics for the scatterer and transmits light. For example, a polymer resin such as an acrylic resin, an imide resin, and/or an epoxy resin may be utilized as the resin included in each of the second-color quantum dot layer **425** and the third-color quantum dot layer **435**.

(49) The scatterer included in each of the second-color quantum dot layer **425** and the third-color quantum dot layer **435** may be particles, for example, light-scattering particles, having a refractive index different from that of the light-transmitting resin included in each of the second-color quantum dot layer **425** and the third-color quantum dot layer **435**. The scatterer is not limited. The scatterer may be capable of forming an optical interface between the scatterer and the light-transmitting resin and of partially scattering transmitted light. For example, the scatterer may be metal oxide particles or organic particles. Examples of a metal oxide for the scatterer may include titanium oxide (TiO_2), zirconium oxide (ZrO_2), aluminum oxide (Al_2O_3), indium oxide (In_2O_3), zinc oxide (ZnO), and/or tin oxide (SnO_2), and examples of an organic material for the scatterer may include an acrylic resin and/or an urethane resin. The scatterer may scatter light in several directions regardless of an angle of incidence without substantially converting a wavelength of incident light. Accordingly, the scatterer may improve side visibility of the display apparatus. Also, the scatterer included in each of the second-color quantum dot layer **425** and the third-color quantum dot layer **435** may increase a chance of light incident on the second-color quantum dot layer **425** and the third-color quantum dot layer **435** to meet (e.g., be incident on or interact with) quantum dots, thereby improving light conversion efficiency.

(50) In the first pixel **PX1**, light having a first wavelength generated by the intermediate layer **303** is emitted to the outside without wavelength conversion. Accordingly, the first pixel **PX1** does not include a quantum dot layer. Hence, a light-transmitting layer **415** formed of a light-transmitting resin is disposed over a first light-emitting device located in the first pixel **PX1**. For example, the light-transmitting layer **415** is disposed over the first pixel electrode **311** of the first light-emitting device located in the first pixel **PX1**. Accordingly, when viewed in the direction (Z-axis direction) perpendicular to the substrate **100** (e.g., when viewed in the plan view), the light-transmitting layer **415** overlaps the first pixel electrode **311**.

(51) The light-transmitting layer **415** may include a scatterer, and any suitable resin included in the light-transmitting layer **415** may be utilized as long as it has suitable dispersion characteristics for the scatterer and transmits light. For example, a polymer resin such as an acrylic resin, an imide resin, and/or an epoxy resin may be utilized as the resin included in the light-transmitting layer **415**.

(52) The scatterer included in the light-transmitting layer **415** may be particles, for example, light-scattering particles, having a refractive index different from that of the light-transmitting resin included in the light-transmitting layer **415**. The scatterer is not particularly limited. For example, the scatterer may be capable of forming an optical interface between the scatterer and the light-transmitting resin and of partially scattering transmitted light. For example, the scatterer may be metal oxide particles or organic particles. Examples of a metal oxide for the scatterer may include titanium oxide (TiO_2), zirconium oxide (ZrO_2), aluminum oxide (Al_2O_3), indium oxide (In_2O_3), zinc oxide (ZnO), and/or tin oxide (SnO_2), and examples of an organic material for the scatterer may include an acrylic resin and/or a urethane resin. The scatterer may scatter light in several directions regardless of an angle of incidence without substantially converting a wavelength of incident light (Lambertian reflection). Accordingly, the scatterer may improve side visibility of the display apparatus.

(53) The light-transmitting layer **415**, the second-color quantum dot layer **425**, and the third-color quantum dot layer **435** are disposed to respectively correspond to the first pixel electrode **311**, the second pixel electrode **321**, and the third pixel electrode **331** as described above. To this end, a barrier layer **401** having through-holes corresponding to the first pixel electrode **311**, the second pixel electrode **321**, and the third pixel electrode **331** may be disposed over the encapsulation layer **500**. In some embodiments, the barrier layer **401** may separate or space apart (e.g., in the plan view) the light-transmitting layer **415**, the second-color quantum dot layer **425**, and the third-color quantum dot layer **435**. When the through-holes of the barrier layer **401** correspond to the first through third pixel electrodes **311**, **321**, and **331**, it means that when viewed in the direction (Z-axis

direction) normal or perpendicular to the substrate **100** (e.g., when viewed in the plan view), the through-holes overlap the first pixel electrode **311**, the second pixel electrode **321**, and the third pixel electrode **331**. In some embodiments, the light-transmitting layer **415**, the second-color quantum dot layer **425**, and the third-color quantum dot layer **435** may be disposed in through-holes of the barrier layer **401** that respectively correspond to the first pixel electrode **311**, the second pixel electrode **321**, and the third pixel electrode **331**. The barrier layer **401** may include (e.g., be) any of various suitable materials, for example, an inorganic material such as silicon oxide, silicon nitride, and/or silicon oxynitride.

(54) A capping layer **403** is disposed over the light-transmitting layer **415**, the second-color quantum dot layer **425**, and the third-color quantum dot layer **435**. The capping layer **403** may be integrally formed to correspond to the first light-emitting device of the first pixel **PX1**, the second light-emitting device of the second pixel **PX2**, and the third light-emitting device of the third pixel **PX3**. The capping layer **403** may include (e.g., be) an inorganic material such as silicon oxide, silicon nitride, and/or silicon oxynitride.

(55) A low refractive index layer **450** is disposed over the capping layer **403**. For example, the low refractive index layer **450** is disposed over the light-transmitting layer **415**, the second-color quantum dot layer **425**, and the third quantum dot layer **435** to correspond to the first light-emitting device of the first pixel **PX1**, the second light-emitting device of the second pixel **PX2**, and the third light-emitting device of the third pixel **PX3**. The low refractive index layer **450** includes a matrix part **451** and a plurality of particles **453** in the matrix part **451**. A first portion **P1** of the low refractive index layer **450** away from the first light-emitting device of the first pixel **PX1**, the second light-emitting device of the second pixel **PX2**, and the third light-emitting device of the third pixel **PX3** (in +Z-axis direction (positive Z-axis direction)) includes fluorine. For example, the matrix part **451** of the first portion **P1** of the low refractive index layer **450** includes fluorine. For example, a first portion of the matrix part **451** corresponding to the first portion **P1** of the low refractive index layer **450** includes fluorine. In some embodiments, the first portion **P1** of the low refractive index layer **450** may be an uppermost portion of the low refractive index layer **450**.

(56) A first-color color filter layer **413**, a second-color color filter layer **423**, and a third-color color filter layer **433** are disposed over the low refractive index layer **450**. For example, the first-color color filter layer **413** is disposed over the low refractive index layer **450** to correspond to the first light-emitting device located in the first pixel **PX1**, the second-color color filter layer **423** is disposed over the low refractive index layer **450** to correspond to the second light-emitting device located in the second pixel **PX2**, and the third-color color filter layer **433** is disposed over the low refractive index layer **450** to correspond to the third light-emitting device located in the third pixel **PX3**. For example, the first-color color filter layer **413** is disposed over the first pixel electrode **311** of the first light-emitting device located in the first pixel **PX1**, the second-color color filter layer **423** is disposed over the second pixel electrode **321** of the second light-emitting device located in the second pixel **PX2**, and the third-color color filter layer **433** is disposed over the third pixel electrode **331** of the third light-emitting device located in the third pixel **PX3**. Accordingly, when viewed in the direction (Z-axis direction) perpendicular to the substrate **100** (e.g., when viewed in the plan view), the first-color color filter layer **413** overlaps the first pixel electrode **311**, the second-color color filter layer **423** overlaps the second pixel electrode **321**, and the third-color color filter layer **433** overlaps the third pixel electrode **331**.

(57) The first-color color filter layer **413** may pass therethrough (e.g., may transmit) only light having a wavelength of about 450 nm to about 495 nm, the second-color color filter layer **423** may pass therethrough (e.g., may transmit) only light having a wavelength of about 495 nm to about 570 nm, and the third-color color filter layer **433** may pass therethrough (e.g., may transmit) only light having a wavelength of about 630 nm to about 780 nm. For example, the first-color color filter layer **413**, the second-color color filter layer **423**, and the third-color color filter layer **433** may respectively transmit only blue light, green light, and red light. The first-color through third-color

color filter layers **413**, **423**, and **433** may reduce reflection of external light in the display apparatus.

(58) For example, when external light reaches the first-color color filter layer **413**, only light having a set or pre-set wavelength passes through the first-color color filter layer **413** as described above, and light having other wavelengths is absorbed by the first-color color filter layer **413**. Accordingly, among external light incident on the display apparatus, only light having a set or pre-set wavelength passes through the first-color color filter layer **413** as described above, and part of the light is reflected at (e.g., on) the counter electrode **305** or at (e.g., on) the first pixel electrode **311** under the first-color color filter layer **413** and is then emitted to the outside again. As a result, because only part of external light incident on a place where the first pixel PX1 is located is reflected to the outside, reflection of the external light may be reduced. This description may also apply to the second-color color filter layer **423** and the third-color color filter layer **433**.

(59) A black matrix **405** including (e.g., being) a carbon black and/or the like may be disposed between the first-color through third-color color filter layers **413**, **423**, and **433**. For example, the black matrix **405** may define, separate and/or space apart (e.g., in the plan view) the first-color through third-color color filter layers **413**, **423**, and **433**. In this case, the black matrix **405** may have through-holes corresponding to the first pixel electrode **311**, the second pixel electrode **321**, and the third pixel electrode **331**, like the barrier layer **401** (e.g., similar to the through-holes of the barrier layer **401**). In some embodiments, the display apparatus does not include the black matrix **405**. In this case, when viewed in the direction (Z-axis direction) perpendicular to the substrate **100** (e.g., when viewed in the plan view), the first-color through third-color color filter layers **413**, **423**, and **433** may at least partially overlap each other between the first pixel PX1, the second pixel PX2, and the third pixel PX3 (e.g., in areas between the first pixel PX1, the second pixel PX2, and the third pixel PX3 in the plan view).

(60) A refractive index (index of refraction) of the low refractive index layer **450** is lower than a refractive index of a layer under (e.g., immediately under) the low refractive index layer **450**. In the display apparatus as shown in FIG. 1, a refractive index of the low refractive index layer **450** is lower than a refractive index of the capping layer **403** under the low refractive index layer **450**. When the capping layer **403** includes (e.g., is) an inorganic material such as silicon oxide, silicon nitride, and/or silicon oxynitride, a refractive index of the capping layer **403** may range from about 1.4 to about 1.5. A refractive index of the low refractive index layer **450** is lower than that of the capping layer **403**, and may range, for example, from about 1.1 to about 1.3. Because a refractive index of the low refractive index layer **450** is lower than a refractive index of a layer under the low refractive index layer **450**, part of light traveling from the capping layer **403** under the low refractive index layer **450** to the low refractive index layer **450** is totally reflected at an interface (e.g., an interface between the capping layer **403** and the low refractive index layer **450**) and travels downward again through the capping layer **403**.

(61) In the second pixel PX2, the totally reflected light travels through the capping layer **403** toward the second-color quantum dot layer **425** under the capping layer **403**. When the totally reflected light is light already converted by the second-color quantum dot layer **425** into light having a wavelength of about 495 nm to about 570 nm, the light is reflected at (e.g., on) the second pixel electrode **321** or at (e.g., on) the counter electrode **305** under the second-color quantum dot layer **425**, passes through the low refractive index layer **450** again, and is emitted to the outside. When the totally reflected light is light that has a wavelength of about 450 nm to about 495 nm and passes through (e.g., has already passed through) the second-color quantum dot layer **425** without being converted by the second-color quantum dot layer **425** into light having a wavelength of about 495 nm to about 570 nm, the totally reflected light may pass through the second quantum dot layer **425** again and may be converted by the second-color quantum dot layer **425** into light having a wavelength of about 495 nm to about 570 nm. Next, the light is reflected at (e.g., on) the second pixel electrode **321** or at (e.g., on) the counter electrode **305** under the second-color quantum dot layer **425**, passes through the low refractive index layer **450** again, and is emitted to the outside.

(62) In the third pixel PX3, the totally reflected light travels through the capping layer 403 toward the third-color quantum dot layer 435 under the capping layer 403. When the totally reflected light is light already converted by the third-color quantum dot layer 435 into light having a wavelength of about 630 nm to about 780 nm, the light is reflected at (e.g., on) the third pixel electrode 331 or at (e.g., on) the counter electrode 305 under the third-color quantum dot layer 435, passes through the low refractive index layer 450 again, and is emitted to the outside. When the totally reflected light is light that has a wavelength of about 450 nm to about 495 nm and passes through (e.g., has already passed through) the third-color quantum dot layer 435 without being converted into light having a wavelength of about 630 nm to about 780 nm, the totally reflected light may pass through the third-color quantum dot layer 435 again and may be converted by the third-color quantum dot layer 435 into light having a wavelength of about 630 nm to about 780 nm. Next, the light is reflected at (e.g., on) the third pixel electrode 331 or at (e.g., on) the counter electrode 305 under the third-color quantum dot layer 435, passes through the low refractive index layer 450 again, and is emitted to the outside.

(63) In the display apparatus according to the present embodiment, because light generated by the second pixel PX2 or the third pixel PX3 is minimized or blocked from being emitted to the outside without being converted by the second-color quantum dot layer 425 or the third-color quantum dot layer 435, luminous efficiency may be significantly improved.

(64) As described above, the low refractive index layer 450 has a refractive index lower than a refractive index of the capping layer 403 which ranges from about 1.4 to about 1.5. For example, a refractive index of the low refractive index layer 450 may range, for example, from about 1.1 to about 1.3. The low refractive index layer 450 includes the matrix part 451 and the plurality of particles 453 in the matrix part 451.

(65) The matrix part 451 may include (e.g., be) a polymer material. The matrix part 451 may include at least one selected from among an acrylic polymer, a silicon-based polymer, a urethane-based polymer, and an imide-based polymer. For example, the matrix part 451 may include (e.g., be) any one polymer material selected from among an acrylic polymer, a silicon-based polymer, a urethane-based polymer, and an imide-based polymer, or a combination of a plurality of polymer materials. Also, the matrix part 451 may include (e.g., be) at least one selected from among a siloxane polymer, a silsesquioxane polymer, an acrylic polymer substituted with a fluorine atom, a silicon-based polymer substituted with a fluorine atom, a urethane-based polymer substituted with a fluorine atom, and an imide-based polymer substituted with a fluorine atom. The matrix part 451 may be formed of siloxane, acryl, polyimide, urethane, and/or epoxy. The matrix part 451 may be formed by solidifying a polymer resin such as siloxane, acryl, polyimide, urethane, and/or epoxy in a high-temperature process and/or an ultraviolet treatment process.

(66) The plurality of particles 453 in the matrix part 451 may be silica. A coating layer formed of an inorganic material may be on surfaces of the plurality of particles 453. The coating layer may include (e.g., be) silicon oxide and/or magnetite (Fe.sub.3O.sub.4). In some embodiments, the plurality of particles 453 may be hollow particles filled with air. When the plurality of particles 453 are hollow particles, the plurality of particles 453 may include silicon oxide, acryl, polyimide, urethane, styrene, and/or epoxy. A refractive index of the plurality of particles 453 may be, for example, equal to greater than 1.1 and equal to or less than 1.3. A refractive index of the low refractive index layer 450 may be equal to or greater than 1.1 and equal to or less than 1.3 by adjusting a refractive index of the low refractive index layer 450 by causing an average diameter of each of the plurality of particles 453 included in the low refractive index layer 450 to be equal to or greater than 20 nm and equal to or less than 150 nm. For example, the average diameter of the plurality of particles 453 may be within the range of about 20 nm to about 150 nm and may be set such that the refractive index of the low refractive index layer 450 is set within the range of 1.1 to 1.3.

(67) In a manufacturing process, after the low refractive index layer 450 is formed, it is useful (e.g.,

necessary) to prevent a refractive index of the low refractive index layer **450** from increasing, or to reduce or minimize an increase of the refractive index of the low refractive index layer **450**. For example, after the low refractive index layer **450** is formed, a process of forming the black matrix **405** and/or the first-color through third-color color filter layers **413**, **423**, and **433** on the low refractive index layer **450** (as shown in FIG. 1) is performed. Because the process of forming the black matrix **405** and/or the first-color through third-color color filter layers **413**, **423**, and **433** utilizes a solution, it is useful (e.g., necessary) to minimize or block the solution from penetrating into the low refractive index layer **450**. This is because, there is a void or the like that is an empty space in the matrix part **451** of the low refractive index layer **450**, and when the solution penetrates into the low refractive index layer **450**, the solution fills the void or the like, thereby increasing a refractive index of the low refractive index layer **450**.

(68) To this end, after the low refractive index layer **450** is formed, it may be considered that an additional capping layer is formed on a top surface (e.g., a surface furthest along the +Z-axis direction) of the low refractive index layer **450** by utilizing silicon oxide, silicon nitride, and/or silicon oxynitride. However, in this case, because a process of forming the additional capping layer has to be performed, a time taken to manufacture the display apparatus increases and a defect rate increases.

(69) However, in the display apparatus according to the present embodiment, in order to simplify a manufacturing process without increasing a refractive index of the low refractive index layer **450** in a subsequent process, the first portion **P1** of the low refractive index layer **450** (e.g., the matrix part **451** of the first portion **P1** of the low refractive index layer **450**) far (e.g., far along the +Z-axis direction) from the first light-emitting device, the second light-emitting device, and the third light-emitting device includes fluorine. The fluorine is a hydrophobic material. Accordingly, the first portion **P1** of the low refractive index layer **450** is hydrophobic. Hence, even when a solution is utilized in a subsequent process after the low refractive index layer **450** is formed, the solution may be prevented or blocked from penetrating into the first portion **P1** of the low refractive index layer **450**, or the penetration of the solution into the first portion **P1** of the low refractive index layer **450** may be minimized. Accordingly, a refractive index of the low refractive index layer **450** may be effectively prevented from increasing after the low refractive index layer **450** is formed, or an increase of the refractive index of the low refractive index layer **450** may be effectively reduced or minimized. A thickness of the first portion **P1** may range, for example, from about 10 nm to about 1000 nm.

(70) When an organic material layer and an inorganic material layer contact each other, stress may occur at an interface and peeling or the like may occur between the organic material layer and the inorganic material layer. However, in the display apparatus according to the present embodiment, a capping layer that is an inorganic material is not added between the low refractive index layer **450** that is an organic material layer and the first-color through third-color color filter layers **413**, **423**, and **433** that are organic material layers. Accordingly, peeling and/or the like due to stress at an interface may be effectively prevented or reduced.

(71) FIGS. 2 and 3 are cross-sectional views illustrating a process of manufacturing the display apparatus of FIG. 1.

(72) As shown in FIG. 2, after the capping layer **403** is formed, a material for forming the low refractive index layer **450** is applied to (e.g., on) the capping layer **403**. The material for forming the low refractive index layer **450** may contain, for example, 80 wt % of solvent and 20 wt % of solid content. Diethylene glycol ethyl methyl ether (MEDG) and/or propylene glycol methyl ether acetate (PGMEA) may be utilized as the solvent. In some embodiments, 50 wt % of the solid content may be a resin, and the remaining 50 wt % of the solid content may be the plurality of particles **453** and a small amount of curing agent and/or dispersant. When the plurality of particles **453** are less than 40 wt % of the solid content, a refractive index of the low refractive index layer **450** may not be sufficiently lowered, and when the plurality of particles **453** are more than 70 wt %

of the solid content, a bonding force with the matrix part **451** may be insufficient and/or dispersibility may be insufficient. Accordingly, the plurality of particles **453** may be equal to or greater than 40 wt % and equal to or less than 70 wt % of the solid content, and in some embodiments may be 50 wt %.

(73) The material for forming the low refractive index layer **450** may not be directly utilized, and a material for forming the low refractive index layer **450** which is finally utilized may be prepared by adding fluorine to the material for forming the low refractive index layer **450**. When the material for forming the low refractive index layer **450** in a liquid state is applied to the capping layer **403**, the plurality of particles **453** are substantially uniformly dispersed in the material for forming the low refractive index layer **450** as shown in FIG. 2.

(74) Next, a thermal curing process is performed. First, pre-baking may be performed at 100° C. for about 50 seconds to about 100 seconds. In this process, most of the solvent is removed. The fluorine in the material for forming the low refractive index layer **450** moves in a direction (+Z-axis direction) away from the capping layer **403**. The fluorine is hydrophobic and thus moves closer to air. For reference, as the fluorine moves closer to the air, the plurality of particles **453** move in a direction (−Z-axis direction (negative Z-axis direction)) opposite to the direction in which the fluorine moves. After the pre-baking, main curing may be performed at 180° C. for about 30 minutes.

(75) After this process, as shown in FIG. 3, the first portion **P1** of the low refractive index layer **450** (e.g., the matrix part **451** of the first portion **P1** of the low refractive index layer **450**) far (e.g., far in the +Z-axis direction) from the first light-emitting device, the second light-emitting device, and the third light-emitting device includes the fluorine. Next, when the black matrix **405** and/or the first-color through third-color color filter layers **413**, **423**, and **433** are formed on the low refractive index layer **450**, because the first portion **P1** of the low refractive index layer **450** (e.g., the matrix part **451** of the first portion **P1** of the low refractive index layer **450**) includes the fluorine that is hydrophobic, a solution utilized in a process of forming the black matrix **405** and/or the first-color through third-color color filter layers **413**, **423**, and **433** may be blocked from penetrating into the low refractive index layer **450**, or an amount of the solution that penetrates into the low refractive index layer **450** may be reduced or minimized. Accordingly, in the display apparatus according to the present embodiment, without performing a process of forming an additional capping layer in addition to a process of forming the low refractive index layer **450**, a refractive index of the low refractive index layer **450** may be effectively prevented from increasing after the low refractive index layer **450** is formed, or an increase of the refractive index of the low refractive index layer **450** may be reduced or minimized. The same effect may be achieved even when ultraviolet curing or the like instead of thermal curing is utilized. This may apply to the following embodiments and modifications thereof.

(76) In the display apparatus according to the present embodiment, a fluorine content per unit volume in the first portion **P1** of the low refractive index layer **450** (e.g., the matrix part **451** of the first portion **P1** of the low refractive index layer **450**) is greater than a fluorine content per unit volume in a second portion **P2** of the low refractive index layer **450** (e.g., the matrix part **451** of the second portion **P2** of the low refractive index layer **450**), for example, a second portion of the matrix part **451** that corresponds to the second portion **P2** of the low refractive index layer **450** close (e.g., close along the −Z-axis direction) to the first through third light-emitting devices in a direction. In some embodiments, the first portion **P1** may be above the second portion **P2** such that the second portion **P2** is between the capping layer **403** and the first portion **P1**. In some embodiments, a fluorine content per unit volume in the first portion **P1** of the low refractive index layer **450** (e.g., the matrix part **451** of the first portion **P1** of the low refractive index layer **450**) is greater than a fluorine content per unit volume in the second portion **P2**, which is closer to the first through third light-emitting devices than the first portion **P1** of the low refractive index layer **450** is to the first through third light-emitting devices. As used herein, when one portion of a first component is

described as being “close to” a second component it may mean, for example, that the one portion is closer to the second component than another portion of the first component is to the second component. As used herein, when one portion of a first component is described as being “away from” or “far from” a second component, it may mean, for example, that the one portion is farther from the second component than another portion of the first component is to the second component.

(77) As described above, the fluorine in the material for forming the low refractive index layer **450** moves in the direction (+Z-axis direction) away from the capping layer **403** in a process of forming the low refractive index layer **450**. Hence, the farther away from the first through third light-emitting devices, the greater a fluorine content per unit volume in the matrix part **451**. For example, the fluorine content per unit volume in the matrix part **451** may increase as it goes from a portion of the matrix part **451** close (e.g., close in the -Z-axis direction) to the first through third light-emitting devices to a portion of the matrix part **451** away (e.g., away in the +Z-axis direction) from the first through third light-emitting devices. For example, the fluorine content per unit volume (e.g., fluorine concentration) may increase in the matrix part **451** along a direction away from the first through third light-emitting devices. For example, the fluorine content per unit volume in the matrix part **451** may increase (e.g., linearly or nonlinearly) along the +Z-axis direction, for example, from a bottom surface of the low refractive index layer **450** to an upper surface of the low refractive index layer **450**. In some embodiments, the fluorine content per unit volume in the matrix part **451** increases with increasing distance away from the first through third light-emitting devices.

(78) A change in a fluorine content in the matrix part **451** may be checked by utilizing various suitable methods. For example, a change in a fluorine content (e.g., fluorine content per unit volume) in a thickness direction (Z-axis direction) in the matrix part **451** may be measured by utilizing time-of-flight secondary-ion mass spectrometry (TOF-SIMS).

(79) As the fluorine moves closer to the air in a thermal curing process as described above, the plurality of particles **453** move in a direction (-Z-axis direction) opposite to the direction in which the fluorine moves. Hence, the number of the plurality of particles **453** per unit volume in the first portion **P1** of the low refractive index layer **450** far (e.g., far along the +Z-axis direction) from the first through third light-emitting devices is less than the number of the plurality of particles **453** per unit volume in the second portion **P2** of the low refractive index layer **450** close (e.g., close along the -Z-axis direction) to the first through third light-emitting devices. For example, the number of the plurality of particles **453** per unit volume in the first portion **P1** of the low refractive index layer **450** far (e.g., far along the +Z-axis direction) from the first through third light-emitting devices is less than the number of the plurality of particles **453** per unit volume in the second portion **P2**, which is closer to the first through third light-emitting devices than the first portion **P1** of the low refractive index layer **450**. For example, the number of the plurality of particles **453** per unit volume in the low refractive index layer may decrease (e.g., linearly or nonlinearly) along the +Z-axis direction, for example, from the bottom surface of the low refractive index layer **450** to the upper surface of the low refractive index layer **450**.

(80) In FIG. 1, the particles **453** hardly exist in the first portion **P1** of the low refractive index layer **450** far (e.g., far along the +Z-axis direction) from the first through third light-emitting devices. However, as shown in FIG. 4, which is a cross-sectional view illustrating a portion of a display apparatus according to another embodiment, some of the particles **453** may be included in the first portion **P1** of the low refractive index layer **450**. This is because, as the amount of fluorine added to the material for forming the low refractive index layer **450** increases to form the low refractive index layer **450**, a thickness of the first portion **P1** including the fluorine may increase.

(81) In the above embodiments, the matrix part **451** is integrally formed from the bottom surface of the low refractive index layer **450** close (e.g., close along the -Z-axis direction) to the first through third light-emitting devices to a top surface of the low refractive index layer **450** far (e.g., far along the +Z-axis direction) from the first through third light-emitting devices. For example, there is no

interface between the first portion P1 and the second portion P2. This is because the first portion P1 and the second portion P2 are not formed through separate processes.

(82) FIG. 5 is a cross-sectional view illustrating a portion of a display apparatus according to another embodiment. The display apparatus according to the present embodiment is different from the display apparatus of FIG. 1 in a position of the capping layer 403 and positions of the first portion P1 and the second portion P2 of the low refractive index layer 450. As shown in FIGS. 1 and 5, the display apparatus according to the present embodiment may also be different from the display apparatus of FIG. 1 in inclined directions of inner surfaces of through-holes of the barrier layer 401 or inner surfaces of through-holes of the black matrix 405.

(83) In the display apparatus according to the present embodiment, the light-transmitting layer 415, the second-color quantum dot layer 425, and the third-color quantum dot layer 435 are disposed over the encapsulation layer 500. The low refractive index layer 450 is disposed over the light-transmitting layer 415, the second-color quantum dot layer 425, and the third-color quantum dot layer 435. For example, the low refractive index layer 450 is disposed over the light-transmitting layer 415, the second-color quantum dot layer 425, and the third-color quantum dot layer 435 to correspond to the first light-emitting device of the first pixel PX1, the second light-emitting device of the second pixel PX2, and the third light-emitting device of the third pixel PX3. The low refractive index layer 450 includes the matrix part 451 and the plurality of particles 453 in the matrix part 451. The first portion P1 of the low refractive index layer 450 (e.g., the matrix part 451 of the first portion P1 of the low refractive index layer 450) close (e.g., close along the -Z-axis direction) to the first light-emitting device of the first pixel PX1, the second light-emitting device of the second pixel PX2, and the third light-emitting device of the third pixel PX3 includes fluorine.

(84) The first-color color filter layer 413, the second-color color filter layer 423, and the third-color color filter layer 433 are disposed over the low refractive index layer 450. In more detail, the first-color color filter layer 413 is disposed over the low refractive index layer 450 to correspond to the first light-emitting device located in the first pixel PX1, the second-color color filter layer 423 is disposed over the low refractive index layer 450 to correspond to the second light-emitting device located in the second pixel PX2, and the third-color color filter layer 433 is disposed over the low refractive index layer 450 to correspond to the third light-emitting device located in the third pixel PX3. For example, the first-color color filter layer 413 is disposed over the first pixel electrode 311 of the first light-emitting device located in the first pixel PX1, the second-color color filter layer 423 is disposed over the second pixel electrode 321 of the second light-emitting device located in the second pixel PX2, and the third-color color filter layer 433 is disposed over the third pixel electrode 331 of the third light-emitting device located in the third pixel PX3. Accordingly, when viewed in the direction (z-axis direction) normal or perpendicular to the substrate 100 (e.g., when viewed in the plan view), the first-color color filter layer 413 overlaps the first pixel electrode 311, the second-color color filter layer 423 overlaps the second pixel electrode 321, and the third-color color filter layer 433 overlaps the third pixel electrode 331.

(85) The capping layer 403 is disposed between the low refractive index layer 450 and the first-color through third-color color filter layers 413, 423, and 433. The capping layer 403 may be integrally formed to correspond to the first light-emitting device of the first pixel PX1, the second light-emitting device of the second pixel PX2, and the third light-emitting device of the third pixel PX3. The capping layer 403 may include (e.g., be) an inorganic material such as silicon oxide, silicon nitride, and/or silicon oxynitride.

(86) A refractive index of the low refractive index layer 450 is lower than a refractive index of a layer under the low refractive index layer 450. In the display apparatus of FIG. 5, a refractive index of the low refractive index layer 450 is lower than a refractive index of each of the second-color quantum dot layer 425 and the third-color quantum dot layer 435 under the low refractive index layer 450. A refractive index of each of the second-color quantum dot layer 425 and the third-color

quantum dot layer **435** may be about 1.7. A refractive index of the low refractive index layer **450** is lower than that of each of the second-color quantum dot layer **425** and the third-color quantum dot layer **435**, and may range, for example, from about 1.1 to about 1.3. Because a refractive index of the low refractive index layer **450** is lower than a refractive index of a layer under the low refractive index layer **450**, part of light traveling from the second-color quantum dot layer **425** and the third-color quantum dot layer **435** under the low refractive index layer **450** to the low refractive index layer **450** is totally reflected at an interface (e.g., an interface between the second-color quantum dot layer **425** and the low refractive index layer **450**, and an interface between the third-color quantum dot layer **435** and the low refractive index layer **450**) and travels again into the second-color quantum dot layer **425** and the third-color quantum dot layer **435**.

(87) In the second pixel PX2, the totally reflected light travels toward the second-color quantum dot layer **425**. When the totally reflected light is light already converted by the second-color quantum dot layer **425** into light having a wavelength of about 495 nm to about 570 nm, the light is reflected at (e.g., on) the second pixel electrode **321** or at (e.g., on) the counter electrode **305** under the second-color quantum dot layer **425**, passes through the low refractive index layer **450** again, and is emitted to the outside. When the totally reflected light is light that has a wavelength of about 450 nm to about 495 nm and passes through (e.g., and has already passed through) the second-color quantum dot layer **425** without being converted by the second-color quantum dot layer **425** into light having a wavelength of about 495 nm to about 570 nm, the totally reflected light may pass through the second-color quantum dot layer **425** again and may be converted by the second-color quantum dot layer **425** into light having a wavelength of about 495 nm to about 570 nm. Next, the light is reflected at (e.g., on) the second pixel electrode **321** or at (e.g., on) the counter electrode **305** under the second-color quantum dot layer **425**, passes through the low refractive index layer **450** again, and is emitted to the outside.

(88) In the third pixel PX3, the totally reflected light travels toward the third-color quantum dot layer **435**. When the totally reflected light is light already converted by the third-color quantum dot layer **435** into light having a wavelength of about 630 nm to about 780 nm, the light is reflected at (e.g., on) the third pixel electrode **331** or at (e.g., on) the counter electrode **305** under the third-color quantum dot layer **435**, passes through the low refractive index layer **450** again, and is emitted to the outside. When the totally reflected light is light that has a wavelength of about 450 nm to about 495 nm and passes through (e.g., has already passed through) the third-color quantum dot layer **435** without being converted by the third-color quantum dot layer **435** into light having a wavelength of about 630 nm to about 780 nm, the totally reflected light may pass through the third-color quantum dot layer **435** again and may be converted by the third-color quantum dot layer **435** into light having a wavelength of about 630 nm to about 780 nm. Next, the light is reflected at (e.g., on) the third pixel electrode **331** or at (e.g., on) the counter electrode **305** under the third-color quantum dot layer **435**, passes through the low refractive index layer **450** again, and is emitted to the outside.

(89) In the display apparatus according to the present embodiment, because light generated by the second pixel PX2 or the third pixel PX3 is minimized or blocked from being emitted to the outside without being converted by the second-color quantum dot layer **425** or the third-color quantum dot layer **435**, luminous efficiency may be significantly improved. To this end, as described above, the low refractive index layer **450** may have a refractive index lower than a refractive index of the capping layer **403** which ranges from about 1.4 to about 1.5. In some embodiments, the low refractive index layer **450** may have a refractive index lower than each of a refractive index of the second-color quantum dot layer **425** and a refractive index of the third-color quantum dot layer **435**, each of which may be about 1.7. For example, a refractive index of the low refractive index layer **450** may range from about 1.1 to about 1.3. The low refractive index layer **450** includes the matrix part **451** and the plurality of particles **453** in the matrix part **451**.

(90) The matrix part **451** may include (e.g., be) a polymer material. The matrix part **451** may

include (e.g., be) at least one selected from among an acrylic polymer, a silicon-based polymer, a urethane-based polymer, and an imide-based polymer. For example, the matrix part **451** may include (e.g., be) any one polymer material selected from among an acrylic polymer, a silicon-based polymer, a urethane-based polymer, and an imide-based polymer, or a combination of a plurality of selected polymer materials. Also, the matrix part **451** may include (e.g., be) at least one selected from among a siloxane polymer, a silsesquioxane polymer, an acrylic polymer substituted with a fluorine atom, a silicon-based polymer substituted with a fluorine atom, a urethane-based polymer substituted with a fluorine atom, and an imide-based polymer substituted with a fluorine atom. The matrix part **451** may be formed of siloxane, acryl, polyimide, urethane, and/or epoxy. The matrix part **451** may be formed by solidifying a polymer resin such as siloxane, acryl, polyimide, urethane, and/or epoxy in a high-temperature process or an ultraviolet treatment process.

(91) The plurality of particles **453** in the matrix part **451** may be silica. A coating layer formed of an inorganic material may be on surfaces of the plurality of particles **453**. The coating layer may include (e.g., be) silicon oxide and/or magnetite (Fe.sub.3O.sub.4). In some embodiments, the plurality of particles **453** may be hollow particles filled with air. When the plurality of particles **453** are hollow particles, the plurality of particles **453** may include (e.g., be) silicon oxide, acryl, polyimide, urethane, styrene, and/or epoxy. A refractive index of the plurality of particles **453** may be, for example, equal to or greater than 1.1 and equal to or less than 1.3. A refractive index of the low refractive index layer **450** may be equal to or greater than 1.1 and equal to or less than 1.3, by adjusting a refractive index of the low refractive index layer **450** by causing an average diameter of each of the plurality of particles **453** included in the low refractive index layer **450** to be equal to or greater than 20 nm and equal to or less than 150 nm.

(92) The first portion **P1** of the low refractive index layer **450** (e.g., the matrix part **451** of the first portion **P1** of the low refractive index layer **450**) close (e.g., close along the -Z-axis direction) to the first light-emitting device, the second light-emitting device, and the third light-emitting device includes fluorine. The fluorine is a hydrophobic material.

(93) FIGS. **6** through **9** are cross-sectional views illustrating a process of manufacturing the display apparatus of FIG. **5**.

(94) As shown in FIG. **6**, the black matrix **405** and/or the first-color through third-color color filter layers **413**, **423**, and **433** are formed on a carrier substrate **10** formed of glass and/or the like. The capping layer **403** is formed of silicon oxide, silicon nitride, and/or silicon oxynitride to cover the black matrix **405** and/or the first-color through third-color color filter layers **413**, **423**, and **433**. After the capping layer **403** is formed, a material for forming the low refractive index layer **450** is applied to the capping layer **403**. The material for forming the low refractive index layer **450** may contain 80 wt % of solvent and 20 wt % of solid content. Diethylene glycol ethyl methyl ether (MEDG) and/or propylene glycol methyl ether acetate (PGMEA) may be utilized as the solvent. 50 wt % of the solid content may be a resin, and the remaining 50 wt % of the solid content may be the plurality of particles **453** and a small amount of curing agent and/or dispersant. When the plurality of particles **453** is less than 40 wt % of the solid content, a refractive index of the low refractive index layer **450** may not be sufficiently lowered, and when the plurality of particles **453** is more than 70 wt % of the solid content, a bonding force with the matrix part **451** may be insufficient and/or dispersibility may be insufficient. Accordingly, the plurality of particles **453** may be equal to or greater than 40 wt % and equal to or less than 70 wt % of the solid content, and preferably may be about 50 wt %.

(95) The material for forming the low refractive index layer **450** may not be directly utilized, and a material for forming the low refractive index layer **450** which is finally utilized may be prepared by adding fluorine to the material for forming the low refractive index layer **450**. When the material for forming the low refractive index layer **450** in a liquid state is applied to (e.g., on) the capping layer **403**, the plurality of particles **453** are substantially uniformly dispersed in the material for

forming the low refractive index layer **450** as shown in FIG. 6.

(96) Next, a thermal curing process is performed. First, pre-baking may be performed at 100° C. for about 50 seconds to about 100 seconds. In this process, most of the solvent is removed. Also, the fluorine in the material for forming the low refractive index layer **450** moves in a direction away from the capping layer **403**. The fluorine is hydrophobic and thus moves closer to air. For reference, as the fluorine moves closer to the air, the plurality of particles **453** move in a direction opposite to the direction in which the fluorine moves. After the pre-baking, main curing may be performed at 180° C. for about 30 minutes.

(97) After this process, as shown in FIG. 7, the first portion **P1** of the low refractive index layer **450** (e.g., the matrix part **451** of the first portion **P1** of the low refractive index layer **450**) far from the capping layer **403** includes the fluorine. Next, as shown in FIG. 8, the light-transmitting layer **415**, the second-color quantum dot layer **425**, and the third-color quantum dot layer **435** are formed on the low refractive index layer **450**. Because a process of forming the light-transmitting layer **415**, the second-color quantum dot layer **425**, and the third-color quantum dot layer **435** utilizes a solution, it is useful (e.g., necessary) to minimize or block the solution from penetrating into the low refractive index layer **450**. This is because, there is a void and/or the like that is an empty space in the matrix part **451** of the low refractive index layer **450**, and when the solution penetrates into the low refractive index layer **450**, the solution fills the void and/or the like, thereby increasing a refractive index of the low refractive index layer **450**.

(98) To this end, after the low refractive index layer **450** is formed, it may be considered that an additional capping layer is formed on a top surface of the low refractive index layer **450** by utilizing silicon oxide, silicon nitride, and/or silicon oxynitride. However, in this case, because a process of forming the additional capping layer has to be performed, a time taken to manufacture the display apparatus increases and a defect rate increases.

(99) However, in the display apparatus according to the present embodiment, as shown in FIGS. 7 and 8, the first portion **P1** of the low refractive index layer **450** (e.g., the matrix part **451** of the first portion **P1** of the low refractive index layer **450**) far from the capping layer **403** includes fluorine. The fluorine is a hydrophobic material. Accordingly, the first portion **P1** of the low refractive index layer **450** is hydrophobic. Hence, even when a solution is utilized in a subsequent process after the low refractive index layer **450** is formed, the solution may be prevented or blocked from penetrating into the first portion **P1** of the low refractive index layer **450**, or the penetration of the solution into the first portion **P1** of the low refractive index layer **450** may be reduced. Accordingly, a refractive index of the low refractive index layer **450** may be effectively prevented from increasing after the low refractive index layer **450** is formed, or an increase of the refractive index of the low refractive index layer **450** may be reduced or minimized. A thickness of the first portion **P1** may range, for example, from about 10 nm to about 1000 nm.

(100) When an organic material layer and an inorganic material layer contact each other, stress may occur at an interface and peeling and/or the like may occur between the organic material layer and the inorganic material layer. However, in the display apparatus according to the present embodiment, a capping layer that is an inorganic material layer is not added between the low refractive index layer **450** that is an organic material layer and the second-color and third-color quantum dot layers **425** and **435** that are organic material layers. Accordingly, peeling and/or the like due to stress at an interface may be effectively prevented or reduced.

(101) After the light-transmitting layer **415**, the second-color quantum dot layer **425**, and the third-color quantum dot layer **435** are formed on the low refractive index layer **450**, the light-transmitting layer **415**, the second-color quantum dot layer **425**, and the third-color quantum dot layer **435** are disposed to face the encapsulation layer **500** as shown in FIG. 9. For example, the light-transmitting layer **415**, the second-color quantum dot layer **425**, and the third-color quantum dot layer **435** may be made to come into contact with the encapsulation layer **500** such that the carrier substrate **10** is an uppermost layer (e.g., in the +Z-axis direction, as shown in FIG. 9). When the

carrier substrate **10** is removed, the display apparatus as shown in FIG. 5 may be manufactured. In order to easily remove the carrier substrate **10**, various suitable modifications may be made. For example, a sacrificial layer may be disposed between the carrier substrate **10** and the first-color through third-color color filter layers **413**, **423**, and **433**. The carrier substrate **10** may not be removed but may be utilized as an encapsulation substrate.

(102) In the display apparatus according to the present embodiment, a fluorine content per unit volume in the first portion **P1** of the low refractive index layer **450** (e.g., the matrix part **451** of the first portion **P1** of the low refractive index layer **450**) is greater than a fluorine content per unit volume in the second portion **P2** of the low refractive index layer **450** (e.g., the matrix part **451** of the second portion **P2** of the low refractive index layer **450**) far from the first through third light-emitting devices. The first portion **P1** may be above the first through third light-emitting devices and the second portion **P2** may be above the first portion **P1** such that the first portion **P1** is between the first through third light-emitting devices and the second portion **P2**. In some embodiments, a fluorine content per unit volume in the first portion **P1** of the low refractive index layer **450** (e.g., the matrix part **451** of the first portion **P1** of the low refractive index layer **450**) is greater than a fluorine content per unit volume in the second portion **P2** (e.g., the matrix part **451** of the second portion **P2** of the low refractive index layer **450**) farther from the first through third light-emitting devices than the first portion **P1** of the low refractive index layer **450**.

(103) As described above, the fluorine in the material for forming the low-refractive-index layer **450** moves in the direction ($-Z$ -axis direction of FIG. 5) away from the capping layer **403** in a process of forming the low-refractive-index layer **450**. Hence, the closer to the first through third light-emitting devices, the greater a fluorine content per unit volume in the matrix part **451**. For example, the fluorine content per unit volume in the matrix part **451** may increase as it goes from a portion of the matrix part **451** away from the first through third light-emitting devices toward the first through third light-emitting devices (e.g., in $-Z$ -axis direction shown in FIG. 5). For example, the fluorine content per unit volume may increase in the matrix part **451** along a direction toward the first through third light-emitting devices. For example, the fluorine content per unit volume in the matrix part **451** may increase (e.g., linearly or nonlinearly) along the $-Z$ -axis direction, for example, from an upper surface of the low refractive index layer **450** to a bottom surface of the low refractive index layer **450**, as shown in FIGS. 5 and 9. In some embodiments, the fluorine content per unit volume in the matrix part **451** increases with decreasing distance away from the first through third light-emitting devices.

(104) As the fluorine moves closer to the air in a thermal curing process as described above, the plurality of particles **453** move in a direction ($+Z$ -axis direction of FIG. 5) opposite to the direction in which the fluorine moves. Hence, the number of the plurality of particles **453** per unit volume in the first portion **P1** of the low refractive index layer **450** close (e.g., close along the $-Z$ -axis direction as in FIG. 5) to the first through third light-emitting devices is less than the number of the plurality of particles **453** per unit volume in the second portion **P2** of the low refractive index layer **450** far (e.g., far along the $+Z$ -axis direction as in FIG. 5) from the first through third light-emitting devices. For example, the number of the plurality of particles **453** per unit volume in the first portion **P1** of the low refractive index layer **450** close (e.g., close along the $-Z$ -axis direction as in FIG. 5) to the first through third light-emitting devices is less than the number of the plurality of particles **453** per unit volume in the second portion **P2** farther from the first through third light-emitting devices than the first portion **P1** of the low refractive index layer **450** is to the first through third light-emitting devices.

(105) For reference, as shown in FIGS. 6 through 8, the first-color through third-color color filter layers **413**, **423**, and **433**, the black matrix **405**, the light-transmitting layer **415**, the second-color color filter layer **425**, the third-color color filter layer **435**, and the barrier layer **401** are formed on the carrier substrate **10**. For example, the barrier layer **401** is formed by forming a layer on the carrier substrate **10** and forming through-holes in the layer. In this case, in a process of forming the

through-holes, an upper portion of the layer in which the through-holes are formed is etched more than a lower portion close to the carrier substrate **10**. For example, as illustrated in FIGS. **6-8**, a through-hole in the barrier layer **401** may have a width and/or planar area at an upper surface that is respectively greater than a width and/or planar area at a lower surface. Accordingly, the area of a surface of the barrier layer **401** close to the carrier substrate **10** is greater than the area of a surface of the barrier layer **401** far from the carrier substrate **10**. For example, as illustrated in FIGS. **6-8**, a planar area of the lower surface of the barrier layer **401** may be greater than a planar area of the upper surface of the barrier layer **401**. Accordingly, in the display apparatus of FIG. **5**, the area of a surface of the barrier layer **401** close (e.g., close along the $-Z$ -axis direction) to the substrate **100** may be less than the area of a surface of the barrier layer **401** far (e.g., far along the $+Z$ -axis direction) from the substrate **100**. For example, as illustrated in FIGS. **5** and **9**, the planar area of the upper surface of the barrier layer **401** may be greater than the planar area of the lower surface of the barrier layer **401**.

(106) However, in the display apparatus of FIG. **1**, because the barrier layer **401** is formed on the encapsulation layer **500**, the area of a surface of the barrier layer **401** close (e.g., close along the $-Z$ -axis direction) to the substrate **100** may be greater than the area of a surface of the barrier layer **401** far (e.g., far along the $+Z$ -axis direction) from the substrate **100**. For example, a planar area of a lower surface of the barrier layer **401** may be greater than a planar area of the upper surface of the barrier layer **401**. For this reason, the display apparatus of FIG. **5** and the display apparatus of FIG. **1** may be different from each other in inclined directions of inner surfaces of through-holes of the barrier layer **401** or inner surfaces of through-holes of the black matrix **405**. For example, as illustrated in the embodiment of FIG. **1**, a normal or perpendicular direction of a side surface of the barrier layer **401** that forms part of a through-hole may have a Z -axis component in the $+Z$ -axis direction. Also, as illustrated in the embodiment of FIG. **5**, a normal direction of a side surface of the barrier layer **401** that forms part of a through-hole may have a Z -axis component in the $-Z$ -axis direction.

(107) In FIG. **5**, the particles **453** hardly exist in the first portion **P1** of the low refractive index layer **450** close (e.g., close along the $-Z$ -axis direction) to the first through third light-emitting devices. However, as shown in FIG. **10**, which is a cross-sectional view illustrating a portion of a display apparatus according to another embodiment, some of the particles **453** may be included in the first portion **P1** of the low refractive index layer **450**. This is because, as the amount of fluorine added to the material for forming the low refractive index layer **450** increases to form the low refractive index layer **450**, a thickness of the first portion **P1** including the fluorine may increase.

(108) When the carrier substrate **10** is not removed and is utilized as an encapsulation substrate, the encapsulation layer **500** may not be required. Accordingly, as shown in FIG. **11**, which is a cross-sectional view illustrating a portion of a display apparatus according to another embodiment, an encapsulation layer may not be disposed but a filler **600** may be disposed between the counter electrode **305** and the light-transmitting layer **415**, the second-color quantum dot layer **425**, and the third-color quantum dot layer **435**. Any of various suitable polymer resins may be utilized as the filler **600**. For example, polyvinyl alcohol, polyvinylpyrrolidone, polyester, polyolefin, methyl methacrylate, polycarbonate, acrylonitrile, cellulose acetate, epoxy, and/or polyurethane may be utilized.

(109) In the above embodiments, the matrix part **451** is integrally formed from a bottom surface of the low refractive index layer **450** close (e.g., close along the $-Z$ -axis direction) to the first through third light-emitting devices to a top surface of the low refractive index layer **450** far (e.g., far along the $+Z$ -axis direction) from the first through third light-emitting devices. For example, the bottom surface of the low refractive index layer **450** may face the first through third light-emitting devices, and the top surface of the low refractive index layer **450** may face oppositely away from the first through third light-emitting devices. For example, there may be no interface between the first portion **P1** and the second portion **P2**. This is because the first portion **P1** and the second portion **P2**

are not formed through separate processes.

(110) According to the one or more embodiments, a display apparatus having high luminous efficiency and a simplified structure may be provided. However, the present disclosure is not limited by such an aspect.

(111) It should be understood that embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features and/or aspects within each embodiment should typically be considered as available for other similar features and/or aspects, respectively, in other embodiments. While one or more embodiments have been described with reference to the drawings, it will be understood by one of ordinary skill in the art that various suitable changes in form and details may be made therein without departing from the spirit and scope as defined by the following claims and equivalents thereof.

Claims

1. A display apparatus comprising: a substrate; a first light-emitting device, a second light-emitting device, and a third light-emitting device, each comprising a first-color emission layer and being over the substrate; a second-color quantum dot layer over the second light-emitting device; a third-color quantum dot layer over the third light-emitting device; a low refractive index layer over the second-color quantum dot layer and the third-color quantum dot layer to correspond to the first through third light-emitting devices, and comprising a matrix part and a plurality of particles in the matrix part, wherein a first portion of the matrix part close to the first through third light-emitting devices comprises fluorine; a first-color color filter layer over the low refractive index layer to correspond to the first light-emitting device; a second-color color filter layer over the low refractive index layer to correspond to the second light-emitting device; and a third-color color filter layer over the low refractive index layer to correspond to the third light-emitting device, wherein the first portion of the matrix part is greater in fluorine content per unit volume than a second portion of the matrix part away from the first through third light-emitting devices.
2. The display apparatus of claim 1, further comprising a light-transmitting layer over the first light-emitting device, wherein the low refractive index layer is over the light-transmitting layer.
3. The display apparatus of claim 1, wherein the second portion of the matrix part is farther from the first through third light-emitting devices than the first portion of the matrix part is to the first through third light-emitting devices.
4. The display apparatus of claim 1, wherein the closer to the first through third light-emitting devices, the greater the fluorine content per unit volume in the matrix part is.
5. The display apparatus of claim 1, wherein the second portion of the matrix part does not comprise fluorine.
6. A display apparatus comprising: a substrate; a first light-emitting device, a second light-emitting device, and a third light-emitting device, each comprising a first-color emission layer and being over the substrate; a second-color quantum dot layer over the second light-emitting device; a third-color quantum dot layer over the third light-emitting device; a low refractive index layer over the second-color quantum dot layer and the third-color quantum dot layer to correspond to the first through third light-emitting devices, and comprising a matrix part and a plurality of particles in the matrix part, wherein a first portion of the matrix part close to the first through third light-emitting devices comprises fluorine; a first-color color filter layer over the low refractive index layer to correspond to the first light-emitting device; a second-color color filter layer over the low refractive index layer to correspond to the second light-emitting device; and a third-color color filter layer over the low refractive index layer to correspond to the third light-emitting device, wherein a first portion of the low refractive index layer close to the first through third light-emitting devices is less in number of the plurality of particles per unit volume than a second portion of the low refractive index layer away from the first through third light-emitting devices.

7. The display apparatus of claim 1, further comprising a capping layer between the low refractive index layer and the first-color through third-color color filter layers to correspond to the first through third light-emitting devices.
 8. The display apparatus of claim 1, wherein the matrix part is integrally formed as a single body from a bottom surface of the low refractive index layer close to the first through third light-emitting devices to a top surface of the low refractive index layer away from the first through third light-emitting devices.
 9. The display apparatus of claim 6, wherein the second portion of the low refractive index layer is farther from the first through third light-emitting devices than the first portion of the low refractive index layer is to the first through third light-emitting devices.
 10. The display apparatus of claim 9, wherein the first portion of the low refractive index layer does not comprise the plurality of particles.
 11. The display apparatus of claim 9, further comprising a light-transmitting layer over the first light-emitting device, wherein the low refractive index layer is over the light-transmitting layer.
 12. The display apparatus of claim 9, wherein the first portion of the matrix part is greater in fluorine content per unit volume than a second portion of the matrix part farther from the first through third light-emitting devices than the first portion of the matrix part is to the first through third light-emitting devices.
 13. The display apparatus of claim 9, further comprising a capping layer between the low refractive index layer and the first-color through third-color color filter layers to correspond to the first through third light-emitting devices.
 14. The display apparatus of claim 9, wherein the matrix part is integrally formed as a single body from a bottom surface of the low refractive index layer close to the first through third light-emitting devices to a top surface of the low refractive index layer away from the first through third light-emitting devices.
-