

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12400872
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Han; Yun et al.

Sacrificial capping layer for gate protection

Abstract

A method includes providing a substrate including metal gate stacks and source/drain contact regions in alternating arrangement along a surface of the substrate with a dielectric spacer separating each source/drain contact region from adjacent metal gate stacks. Each source/drain region is recessed within an opening between adjacent metal gate stacks such that source/drain contact regions provide a bottom of the recess and dielectric spacers provide sidewalls. The etch stop layer is formed on the substrate such that it conformally covers the metal gate stacks, the sidewalls and the bottom of each recess, and a sacrificial layer is formed over each of the metal gate stacks and on at least a portion of each sidewall. The etch stop layer is removed from the bottom of each recess to expose the source/drain contact, and the sacrificial layer is then removed from the metal gate stacks and the sidewalls of each recess.

Inventors: Han; Yun (Albany, NY), O'Meara; David L (Albany, NY), Alix; Cheryl (Albany, NY), Metz; Andrew (Albany, NY), Hu; Shan (Albany, NY), Zhang; Henan (Albany, NY)

Applicant: Tokyo Electron Limited (Tokyo, JP)

Family ID: 1000008779804

Assignee: Tokyo Electron Limited (Tokyo, JP)

Appl. No.: 17/724088

Filed: April 19, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20220344169 A1	Oct. 27, 2022

Related U.S. Application Data

Publication Classification

Int. Cl.: **H01L21/311** (20060101); **H01L21/02** (20060101); **H01L21/768** (20060101);
H10D30/01 (20250101); **H10D30/62** (20250101); **H10D64/01** (20250101)

U.S. Cl.:

CPC **H01L21/31144** (20130101); **H01L21/02186** (20130101); **H01L21/0228** (20130101);
H01L21/31116 (20130101); **H01L21/76802** (20130101); **H01L21/76831** (20130101);
H10D30/024 (20250101); H10D30/6219 (20250101); H10D64/017 (20250101)

Field of Classification Search

CPC: H01L (21/31144); H01L (21/02186); H01L (21/0228); H01L (21/31116); H01L
(21/76802); H01L (21/76831); H01L (29/41791); H01L (29/66545); H01L (29/66795);
H01L (21/76897); H01L (29/7848); H01L (2221/1063)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
10037884	12/2017	Ou	N/A	H01L 21/02266
10497858	12/2018	Ahn	N/A	G11C 11/161
2004/0171201	12/2003	Gambino et al.	N/A	N/A
2006/0183277	12/2005	Brask et al.	N/A	N/A
2007/0161169	12/2006	Belyansky	257/E21.415	H01L 29/66772
2016/0268312	12/2015	Wang et al.	N/A	N/A
2016/0293838	12/2015	Swaminathan	N/A	H01L 21/02186
2016/0372324	12/2015	Kao	N/A	H01L 21/0337
2017/0047253	12/2016	Park	N/A	H01L 21/31105
2019/0140066	12/2018	Lee	N/A	H01L 29/0673
2020/0098919	12/2019	Peng et al.	N/A	N/A
2020/0168464	12/2019	Loh	N/A	N/A

OTHER PUBLICATIONS

Korean Intellectual Property Office, International Search Report and Written Opinion for
International application No. PCT/US2022/025969, mailed Aug. 11, 2022, 8pp. cited by applicant

Primary Examiner: Page; Dale E

Assistant Examiner: Tivarus; Cristian A

Attorney, Agent or Firm: Oblon, McClelland, Maier & Neustadt, L.L.P.

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) The present disclosure claims the benefit of U.S. Provisional Application No. 63/179,098 filed Apr. 23, 2021, which is incorporated herein by reference in its entirety.

TECHNICAL FIELD

(1) The present invention relates generally to semiconductor device fabrication, and more particularly, to methods for forming a sacrificial capping layer for gate protection.

BACKGROUND

(2) Advancement in semiconductor technologies relies on continued improvement in manufacturing fabrication technology. Innovation in semiconductor technologies has resulted in the introduction of new types of structures such as FinFET devices, stacked structures (e.g., 3D NAND devices). However, these new structures introduce a need for new fabrication schemes to overcome, what would otherwise be, debilitating manufacturing challenges. The present inventors recognized one such challenge which arises from damage to cap layers as well as erosion of spacers on gate sidewalls as a result of semiconductor plasma processing techniques. For instance, a dry etch process such as reactive Ion etching (RIE) may be used to open contacts within traditional middle-of-line (MOL) process flow. Often, the dry etch process can be quite aggressive for some layers within a semiconductor process flow. Typically, the dry etch process possesses a plasma source that generates a sea of ions that accelerate in a manner that causes ion bombardment against sensitive device layers. Resultantly, the plasma etch processes may cause damage to the underlying material, especially when opening high aspect ratio contact holes. This damage to the underlying material can then lead to uncontrolled variations in device electrical performance, as well as yield loss.

SUMMARY

(3) The present disclosure relates to a semiconductor device, and a method of manufacturing a semiconductor device.

(4) An aspect (1) provides a method including providing a substrate including a plurality of metal gate stacks and a plurality of source/drain contact regions in alternating arrangement along a surface of the substrate with a dielectric spacer separating each source/drain contact region from an adjacent metal gate stack. Each of the source/drain regions is recessed within an opening between adjacent metal gates stacks such that the source/drain contact regions provide a bottom of the recess and the dielectric spacers provide sidewalls of the recess. The etch stop layer is formed on the substrate such that the etch stop layer conformally covers the plurality of metal gate stacks, the sidewalls of each recess and the bottom of each recess, and a sacrificial layer is formed over each of the metal gate stacks and on at least a portion of each sidewall of each recess. The etch stop layer is removed from the bottom of each recess to expose the source/drain contact, and the sacrificial layer is then removed from each of the metal gate stacks and from the sidewalls of each recess.

(5) An aspect (2) includes the method of aspect (1), wherein the forming a sacrificial layer includes forming the sacrificial layer having a first thickness on top of each metal gate stack and a second thickness on the sidewalls of each recess, the first thickness being greater than the second thickness.

(6) An aspect (3) includes the method of aspect (1), wherein the forming a sacrificial layer includes forming the sacrificial layer on each sidewall such that a thickness of the sacrificial layer decreases from the upper portion of the recess toward the bottom of the recess.

(7) An aspect (4) includes the method of aspect (1), wherein the forming a sacrificial layer includes preferentially forming the sacrificial layer on top of each metal gate stack relative to sidewalls of each recess.

(8) An aspect (5) includes the method of aspect (4), wherein the preferentially forming the sacrificial layer includes performing an atomic layer deposition (ALD) process under processing conditions that reduce diffusion of reactant gases into the recesses.

- (9) An aspect (6) includes the method of aspect (5), wherein the processing conditions include at least one of concentrations of the reactant gases, gas exposure times, substrate temperature, and substrate rotation speed.
- (10) An aspect (7) includes the method of aspect (4), wherein the preferentially forming the sacrificial layer includes rotating the substrate while exposing the substrate to gas for forming the sacrificial layer.
- (11) An aspect (8) includes the method of aspect (7), further including setting a rotation speed of the substrate to provide a predetermined preferential deposition of the sacrificial layer on a top of each metal gate stack.
- (12) An aspect (9) includes the method of aspect (1), wherein the forming an etch stop layer includes forming a layer including silicon nitride, silicon oxide, or silicon oxynitride.
- (13) An aspect (10) includes the method of aspect (1), wherein the forming a sacrificial layer includes forming a layer including a metal oxide (MOx), a metal nitride (MNx), or a metal oxynitride.
- (14) An aspect (11) includes the method of aspect (4), wherein the preferentially forming a sacrificial layer includes forming a sacrificial capping layer having a thickness ranging from 0.5 nm to about 10 nm on the top of each metal gate stack.
- (15) An aspect (12) includes the method of aspect (11), wherein the preferentially forming a sacrificial layer includes forming a sacrificial capping layer having a thickness ranging from 2 nm to about 5 nm on the top of each metal gate stack.
- (16) Another aspect (13) provides a method including providing a substrate including a source/drain contact region, a replacement metal gate stack, a spacer on a sidewall of the replacement metal gate stack, and an etch stop layer on the spacer. A sacrificial capping layer is formed on the replacement metal gate stack, the sacrificial capping layer having a first thickness on top of the replacement metal gate stack and a second thickness on the etch stop layer, the first thickness being greater than the second thickness. The etch stop layer is removed using a plasma etching process, and the sacrificial capping layer is removed.
- (17) An aspect (14) includes the method of aspect (13), wherein the etch stop layer contains silicon nitride, silicon oxide, or silicon oxynitride.
- (18) An aspect (15) includes the method of aspect (13), wherein the sacrificial capping layer includes a metal oxide (MOx), a metal nitride (MNx), or a metal oxynitride.
- (19) An aspect (16) includes the method of aspect (13), wherein the sacrificial capping layer includes AlN, TiN, or TiOx.
- (20) An aspect (17) includes the method of aspect (13), wherein the substrate is rotated during the forming of the sacrificial capping layer.
- (21) An aspect (18) includes the method of aspect (13), wherein removing the sacrificial capping layer includes using a wet etch chemistry.
- (22) Another aspect (19) provides a method which includes providing a substrate including a source/drain contact region, a replacement metal gate (RMG) stack, a low-k spacer on a sidewall of the replacement metal gate stack, and an etch stop layer on the spacer. A sacrificial capping layer containing TiO₂ is formed on the replacement metal gate stack, the sacrificial capping layer having a first thickness on top of the replacement metal gate stack and a second thickness on the etch stop layer, the first thickness being greater than the second thickness. The etch stop layer is removed using a plasma etching process, and the sacrificial capping layer is removed using wet etch chemistry.
- (23) An aspect (20) includes the method of aspect (19), wherein the forming a sacrificial capping layer includes preferentially deposited on the top of each the RMG stack by atomic layer deposition (ALD) using sequential exposures of titanium tetrakis(dimethylamido)titanium (TDMA) and ozone (O₃) at a process pressure between about 1 Torr and about 3 Torr, a substrate temperature between about 100° C. and about 150° C., and a substrate rotation speed between about 10 RPM and about

(24) Note that this summary section does not specify every embodiment and/or incrementally novel aspect of the present disclosure or claimed disclosure. Instead, this summary only provides a preliminary discussion of different embodiments and corresponding points of novelty over conventional techniques. For additional details and/or possible perspectives of the present disclosure and embodiments, the reader is directed to the Detailed Description section and corresponding figures of the present disclosure as further discussed below.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be increased or reduced for clarity of discussion.

(2) FIG. 1A illustrates a partial cross sectional fin view of a semiconductor device during fabrication along a direction of a fin, FIG. 1B shows a cross sectional gate view of the semiconductor device along a direction orthogonal to the direction of the fin, and in accordance with an example embodiment of the present disclosure; and FIG. 1C illustrates a top view of the semiconductor in accordance with an example embodiment of the present disclosure;

(3) FIGS. 2A-2B illustrate cross sectional fin and gate views respectively of the semiconductor device during a subsequent stage of fabrication, in accordance with an example embodiment of the present disclosure;

(4) FIGS. 3A-3B illustrate cross sectional fin and gate views respectively of the semiconductor device during a subsequent stage of fabrication, in accordance with an example embodiment of the present disclosure;

(5) FIGS. 4A-4B illustrate cross sectional fin and gate views respectively of the semiconductor device during a subsequent stage of fabrication, in accordance with an example embodiment of the present disclosure;

(6) FIGS. 5A-5B illustrate cross sectional fin and gate views respectively of the semiconductor device during a subsequent stage of fabrication, in accordance with an example embodiment of the present disclosure;

(7) FIGS. 6A-6B illustrate cross sectional fin and gate views respectively of the semiconductor device during a subsequent stage of fabrication, in accordance with an example embodiment of the present disclosure;

(8) FIGS. 7A-7B illustrate cross sectional fin and gate views respectively of the semiconductor device during a subsequent stage of fabrication, in accordance with an example embodiment of the present disclosure; and

(9) FIGS. 8A-8B illustrate partial cross sectional views of the semiconductor device **100** during a next stage of fabrication, after removing the sacrificial capping layer **110**, in accordance with an example embodiment of the present disclosure.

DETAILED DESCRIPTION OF ILLUSTRATIVE EMBODIMENTS

(10) The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and

second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed. Further, spatially relative terms, such as “top,” “bottom,” “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(11) Embodiments of the present application disclose a method for preventing damage to semiconductor regions during plasma etching. The proposed integration scheme uses a sacrificial capping layer formed directly on top of a semiconductor region to be protected. This sacrificial capping layer is designed to protect the semiconductor region during the plasma etching process that would otherwise damage the semiconductor region. This sacrificial capping layer may be removed later in the process using a gentle wet clean process.

(12) Embodiments of the application may be applied to various types of devices such as Fin transistors as well as stacked memory devices. Specific embodiments of the above process will be described using FIGS. 1-8 below.

(13) FIG. 1A illustrates a partial cross sectional view of a semiconductor device during fabrication along a direction of a fin, and FIG. 1B shows a cross sectional view of the semiconductor device along a direction orthogonal to the direction of the fin. FIG. 1C illustrates a top view showing the outline 1A-1A illustrated in FIG. 1A and outline 1B-1B illustrated in FIG. 1B, all in accordance with an embodiment of the present invention. FIG. 1A is a partial cross sectional view and does not show the underlying fins and substrate.

(14) As illustrated in FIGS. 1A-1C, at this stage of processing, the semiconductor device **100** has already gone through a substantial part of the front-end-of-the-line (FEOL) fabrication. For example, as illustrated in FIG. 1B, a transistor structure with a plurality of fins **109** is formed on the substrate **111**.

(15) In various embodiments, the substrate **111** may comprise silicon, silicon germanium, silicon carbide, and compound semiconductors such as gallium nitride, gallium arsenide, indium arsenide, indium phosphide, and others. The substrate **111** may comprise a semiconductor wafer that may include a semiconductor epitaxial layer including hetero epitaxial layers. For example, in one or more embodiments, one or more hetero epitaxial layers comprising a compound semiconductor may be formed over a semiconductor substrate. In various embodiments, a portion or an entirety of the substrate **111** may be amorphous, polycrystalline, or single-crystalline. In various embodiments, the substrate **111** may be doped, undoped, or contain both doped and undoped regions.

(16) The plurality of fins **109** may be formed by epitaxial growth from the substrate **111** or alternatively using an etch back process leaving the plurality of fins **109**. The plurality of fins **109** may be isolated from each other by shallow isolation regions **112**. Accordingly, the shallow isolation regions **112** and the plurality of fins **109** may form an alternating pattern.

(17) In one embodiment, the shallow isolation regions **112** may be formed by depositing an oxide fill material after patterning the plurality of fins **109**, which is then planarized, for example, using a chemical mechanical planarization process. After a planarization, the shallow isolation regions **112** may be recessed so as to raise the plurality of fins **109**.

(18) A plurality of dummy gates **102** are formed over the substrate **111** and the plurality of fins **109**. In one embodiment, the plurality of dummy gates **102** may be formed by patterning a layer of amorphous silicon or polysilicon deposited over the plurality of fins **109**.

(19) Next, a plurality of spacers **101** are formed on sidewalls of the plurality of dummy gates **102**. The plurality of spacers **101** can be formed by depositing an insulating layer followed by an

anisotropic etching process. For example, a reactive ion etch (RIE) process may be used to form the spacers **101**. The material of the insulating layer is chosen to be selectively not etched during the removal of the plurality of dummy gates **102** later in the process, e.g., immune to etching by chemical such as TMAH or NH_4OH . In one example, the spacers **101** can contain a low-k material.

(20) Next, epitaxial regions **103** are grown over portions of the plurality of fins **109** located between the plurality of dummy gates **102** so as to form raised source/drain regions. The upper surface of the raised source/drain regions may form a faceted surface due to the growth pattern of the corresponding epitaxial material.

(21) In one or more embodiments, the epitaxial regions **103** may be formed in a single epitaxial growth process. In other embodiments, the growth of the epitaxial regions **103** may consist of a multi-stage process. For example, it can begin with growing an initial epitaxial layer with a first doping on the plurality of fins **109** to a pre-determined thickness followed by the growth of a second layer with a second doping. For example, the second doping may be higher than the first doping. Similarly, the different layer may have different compositions of e.g., germanium or other compounds. The epitaxial growth process may use any type of epitaxial process including molecular beam epitaxy (MBE), or various types of chemical vapor deposition (CVD).

(22) In one or more embodiments, the epitaxial regions **103** may be grown to introduce strain into the plurality of fins **109**, for example, due to lattice mismatch.

(23) In one or more embodiments, the source/drain (S/D) regions may be formed by doping the regions of the fins and the epitaxial regions **103**, for example, with an implantation/anneal process.

(24) FIGS. 2A-2B illustrate a cross sectional view of the semiconductor device **100**, during a subsequent stage of fabrication, after forming etch stop layer (ESL) **105** over the semiconductor device **100**. FIG. 2A illustrates a cutline similar to FIG. 1A while FIG. 2B illustrates a cutline similar to FIG. 1B.

(25) The ESL **105** may be conformally deposited across the entire wafer surface. In various embodiments, the ESL **105** comprises silicon nitride, silicon oxide, or silicon oxynitride. In various embodiments, the ESL **105** may have a thickness ranging from 0.5 nm to about 10 nm. In one embodiment, the ESL **105** may have a thickness ranging from 2 nm to about 5 nm.

(26) FIGS. 3A-3B illustrate partial cross sectional views of the semiconductor device **100** during fabrication after depositing an oxide **106** in accordance with an embodiment of the present invention. FIG. 3A illustrates a cutline similar to FIG. 1A while FIG. 3B illustrates a cutline similar to FIG. 1B.

(27) Referring to FIGS. 3A and 3B, the oxide **106** is filled between the plurality of dummy gates **102**. The oxide **106** is overfilled above the top surface of the ESL **105** and over the plurality of dummy gates **102**.

(28) In various embodiments of semiconductor device **100**, the oxide **106** may be a flowable oxide including spin-on-glass. In one example, a layer comprising borophosphosilicate glass (BPSG), phosphosilicate glass (PSG), borosilicate glass (BSG), arsenic-silicon glass (ArSG), or other types of glass may be deposited and heated to reflow. In one or more embodiments, the oxide **106** may also comprise an oxide such as tetra ethyl oxysilane (TEOS), fluorinated TEOS (FTEOS), organo silicate glass (OSG), fluorinated silicate glass (FSG), or a spin-on glass (SOG).

(29) FIGS. 4A-4B illustrate a cross sectional view of the semiconductor device **100** during fabrication after forming a replacement metal gate (RMG) in accordance with an embodiment of the invention. FIG. 4A illustrates a cutline similar to FIG. 1A while FIG. 4B illustrates a cutline similar to FIG. 1B.

(30) As illustrated in FIGS. 4A and 4B, the oxide **106** is planarized to expose the underlying ESL **105**. The ESL **105** may be removed using an anisotropic etching process to expose the plurality of dummy gates **102**. The plurality of dummy gates **102** is then removed, e.g., using a wet etch process or alternatively a plasma process. The spacer **101** retains the shape of the gate stack during

the removal of the plurality of dummy gates **102**. During the etching process, the oxide **106** protects the underlying regions of the epitaxial region **103**.

(31) After removing the plurality of dummy gates **102**, the inner sidewalls of the plurality of spacers **101** are exposed leaving a cavity. This cavity is filled with a replacement gate material **107**. After the replacement gate material **107** is in place, a contact cap **108** is formed. The contact cap **108** may be formed using a self-aligned process so as to form selectively only over the replacement gate material **107**.

(32) The replacement gate material **107** along with the contact cap **108** form the replacement metal gate (RMG) stack **102'**. The RMG stack **102'** helps to set the work function of the gate and forms the final gate electrode of the semiconductor device **100**.

(33) FIGS. 5A-5B illustrate partial cross sectional views of the semiconductor device **100** during a next stage of fabrication, after etching of the oxide **106**, in accordance with an embodiment of the present invention. FIG. 5A illustrates a cutline similar to FIG. 1A while FIG. 5B illustrates a cutline similar to FIG. 1B.

(34) As illustrated in FIG. 5A, the etching of the oxide **106** leaves empty, unfilled trenches or recessed features behind. In various embodiments, the oxide etch process may be a wet etch process, or a dry etch process such as reactive ion etch (RIE), or any process currently known within the art of semiconductor manufacturing. Etching the oxide **106** exposes the ESL **105** remaining between the plurality of spacers **101** that line the replacement gate material **107** and the contact cap **108**.

(35) FIGS. 6A-6B illustrate partial cross sectional views of the semiconductor device **100** during a next stage of fabrication, after depositing a sacrificial capping layer **110**, in accordance with an embodiment of the present invention. FIG. 6A illustrates a cutline similar to FIG. 1A while FIG. 6B illustrates a cutline similar to FIG. 1B.

(36) The sacrificial capping layer **110** may be preferentially deposited on the top of the RMG stack **102'** containing the contact cap **108** and the replacement gate material **107**. As schematically depicted in FIGS. 6A-6B, a thickness of the sacrificial capping layer **110** can be greater on the contact cap **108** than on the ESL **105** on the spacer **101**, and the thickness of the sacrificial capping layer **110** on the ESL **105** spacer **101** can decrease from the upper portion of the spacer **101** to the lower portion of the spacer **101**. In various embodiments, the sacrificial capping layer **110** can include either metal oxides (MO_x), metal nitrides (MN_x), and metal oxynitrides such as, AlO_x, AlN, TiN, TiO_x, etc., where the "M" represents an elemental metal such as aluminum, titanium, tantalum, and others.

(37) In various embodiments, the sacrificial capping layer **110** may have a thickness ranging from 0.5 nm to about 10 nm on the top of the contact cap **108**. In one embodiment, the sacrificial capping layer **110** may have a thickness ranging from 2 nm to about 5 nm.

(38) In one embodiment of the semiconductor device **100**, the sacrificial capping layer **110** is formed using a vapor phase deposition process, for example an atomic layer deposition (ALD) process, a chemical vapor deposition process such as metal-organic CVD (MOCVD) and other such processes.

(39) In one embodiment, the preferential deposition of the sacrificial capping layer **110** on the top of the RMG stack **102'** may be achieved using an ALD process and processing conditions that reduce diffusion of the reactant gases into the trenches or recessed features between the plurality of RMG stacks **102'**. Processing conditions can include concentrations of the reactant gases, gas exposure times, substrate temperature, and substrate rotation speed. In one example, the substrate may be rotated during the gas exposures and the rotation speed optimized for achieving the desired preferential deposition. In some examples, a higher rotation speed can result in increased preferential deposition on the top of the RMG stack **102'**. Thus, the shape of the sacrificial capping layer **110** is tunable and the sacrificial capping layer **110** may have a first thickness on top of the replacement metal gate stack and a second thickness on the etch stop layer, the first thickness being

greater than the second thickness.

(40) In one example, a sacrificial capping layer **110** containing TiO.sub.2 that is preferentially deposited on the top of the RMG stack **102'** may be deposited by ALD using sequential exposures of titanium tetrakis(dimethylamido)titanium (TDMAT) and ozone (O.sub.3) at a process pressure between about 1 Torr and about 3 Torr, a substrate temperature between about 100° C. and about 150° C., and a rotation speed between about 10 RPM and about 50 RMP.

(41) FIGS. 7A-7B illustrate partial cross sectional views of the semiconductor device **100** during a next stage of fabrication, after performing a ESL etching process, in accordance with an embodiment of the present invention. FIG. 7A illustrates a cutline similar to FIG. 1A while FIG. 7B illustrates a cutline similar to FIG. 1B.

(42) The ESL etching process removes the remaining ESL **105** on the plurality of spacers **101** that line the replacement gate material **107** and the contact cap **108**.

(43) In various embodiments, the remaining ESL **105** is removed using a plasma process such as a reactive ion etching (RIE) process. The RIE process can have poor etch selectivity to the contact cap **108** and the spacers **101** and the sacrificial capping layer **110** protects the contact cap **108** and the underlying plurality of spacers **101** from plasma damage during the highly anisotropic ME process.

(44) FIGS. 8A-8B illustrate partial cross sectional views of the semiconductor device **100** during a next stage of fabrication, after removing the sacrificial capping layer **110**, in accordance with an embodiment of the present invention. FIG. 8A illustrates a cutline similar to FIG. 1A while FIG. 8B illustrates a cutline similar to FIG. 1B.

(45) The removal of the sacrificial capping layer **110** may be performed by an etching process, for example wet etching, that is efficient and does not damage the contact cap **108**, the plurality of spacers **101**, and the epitaxial regions **103**. In one example, wet etching can include a sulfuric peroxide mix (SPM) between about 70° C. and about 110° C.

(46) In the preceding description, specific details have been set forth, such as a particular geometry of a processing system and descriptions of various components and processes used therein. It should be understood, however, that techniques herein may be practiced in other embodiments that depart from these specific details, and that such details are for purposes of explanation and not limitation. Embodiments disclosed herein have been described with reference to the accompanying drawings. Similarly, for purposes of explanation, specific numbers, materials, and configurations have been set forth in order to provide a thorough understanding. Nevertheless, embodiments may be practiced without such specific details. Components having substantially the same functional constructions are denoted by like reference characters, and thus any redundant descriptions may be omitted.

(47) Various techniques have been described as multiple discrete operations to assist in understanding the various embodiments. The order of description should not be construed as to imply that these operations are necessarily order dependent. Indeed, these operations need not be performed in the order of presentation. Operations described may be performed in a different order than the described embodiment. Various additional operations may be performed and/or described operations may be omitted in additional embodiments.

(48) "Substrate" or "wafer" as used herein generically refers to an object being processed in accordance with the invention. The substrate may include any material portion or structure of a device, particularly a semiconductor or other electronics device, and may, for example, be a base substrate structure, such as a semiconductor wafer, reticle, or a layer on or overlying a base substrate structure such as a thin film. Thus, substrate is not limited to any particular base structure, underlying layer or overlying layer, patterned or un-patterned, but rather, is contemplated to include any such layer or base structure, and any combination of layers and/or base structures. The description may reference particular types of substrates, but this is for illustrative purposes only.

(49) Those skilled in the art will also understand that there can be many variations made to the

operations of the techniques explained above while still achieving the same objectives of the invention. Such variations are intended to be covered by the scope of this disclosure. As such, the foregoing descriptions of embodiments of the invention are not intended to be limiting. Rather, any limitations to embodiments of the invention are presented in the following claims.

Claims

1. A method comprising: providing a substrate comprising a plurality of metal gate stacks and a plurality of source/drain contact regions in alternating arrangement along a surface of the substrate with a dielectric spacer separating each source/drain contact region from an adjacent metal gate stack, wherein each of the source/drain regions is recessed within an opening between adjacent metal gates stacks such that the source/drain contact regions provide a bottom of the recess and the dielectric spacers provide sidewalls of the recess; forming an etch stop layer on the substrate such that the etch stop layer conformally covers the plurality of metal gate stacks, the sidewalls of each recess and the bottom of each recess; forming a sacrificial layer over each of the metal gate stacks and on at least a portion of each sidewall of each recess; removing the etch stop layer from the bottom of each recess while the sacrificial layer remains on at least a portion of each sidewall of each recess to expose the source/drain contact; and removing the sacrificial layer from each of the metal gate stacks and from the sidewalls of each recess.
2. The method of claim 1, wherein the forming a sacrificial layer comprises forming the sacrificial layer having a first thickness on top of each metal gate stack and a second thickness on the sidewalls of each recess, the first thickness being greater than the second thickness.
3. The method of claim 1, wherein the forming a sacrificial layer comprises forming the sacrificial layer on each sidewall such that a thickness of the sacrificial layer decreases from the upper portion of the recess toward the bottom of the recess.
4. The method of claim 1, wherein the forming a sacrificial layer comprises preferentially forming the sacrificial layer on top of each metal gate stack relative to sidewalls of each recess.
5. The method of claim 4, wherein the preferentially forming the sacrificial layer comprises performing an atomic layer deposition (ALD) process under processing conditions that reduce diffusion of reactant gases into the recesses.
6. The method of claim 5, wherein the processing conditions comprise at least one of concentrations of the reactant gases, gas exposure times, substrate temperature, and substrate rotation speed.
7. The method of claim 4, wherein the preferentially forming the sacrificial layer comprises rotating the substrate while exposing the substrate to gas for forming the sacrificial layer.
8. The method of claim 7, further comprising setting a rotation speed of the substrate to provide a predetermined preferential deposition of the sacrificial layer on a top of each metal gate stack.
9. The method of claim 1, wherein the forming an etch stop layer comprises forming a layer comprising silicon nitride, silicon oxide, or silicon oxynitride.
10. The method of claim 1, wherein the forming a sacrificial layer comprises forming a layer comprising a metal oxide (MO_x), a metal nitride (MN_x), or a metal oxynitride.
11. The method of claim 4, wherein the preferentially forming a sacrificial layer comprises forming a sacrificial capping layer having a thickness ranging from 0.5 nm to about 10 nm on the top of each metal gate stack.
12. The method of claim 11, wherein the preferentially forming a sacrificial layer comprises forming a sacrificial capping layer having a thickness ranging from 2 nm to about 5 nm on the top of each metal gate stack.
13. A method comprising: providing a substrate comprising a source/drain contact region, a replacement metal gate stack, a spacer on a sidewall of the replacement metal gate stack, and an etch stop layer on the spacer; forming a sacrificial capping layer on the replacement metal gate

stack, the sacrificial capping layer having a first thickness on top of the replacement metal gate stack and a second thickness on the etch stop layer, the first thickness being greater than the second thickness, the sacrificial capping layer being formed on only a portion of the replacement metal gate stack such that an exposed portion of the etch stop layer is exposed; removing the exposed portion of the etch stop layer using a plasma etching process while the sacrificial capping layer remains on the etch stop layer; and removing the sacrificial capping layer.

14. The method of claim 13, wherein the etch stop layer contains silicon nitride, silicon oxide, or silicon oxynitride.

15. The method of claim 13, wherein the sacrificial capping layer includes a metal oxide (MOx), a metal nitride (MNx), or a metal oxynitride.

16. The method of claim 13, wherein the sacrificial capping layer includes AlN, TiN, or TiOx.

17. The method of claim 13, wherein the substrate is rotated during the forming of the sacrificial capping layer.

18. The method of claim 13, wherein removing the sacrificial capping layer includes using a wet etch chemistry.

19. A method comprising: providing a substrate comprising a source/drain contact region, a replacement metal gate (RMG) stack, a low-k spacer on a sidewall of the replacement metal gate stack, and an etch stop layer on the spacer; forming a sacrificial capping layer containing TiO₂ on the replacement metal gate stack, the sacrificial capping layer having a first thickness on top of the replacement metal gate stack and a second thickness on the etch stop layer, the first thickness being greater than the second thickness, the sacrificial capping layer being formed on only a portion of the replacement metal gate stack such that an exposed portion of the etch stop layer is exposed; removing the exposed portion of the etch stop layer using a plasma etching process while the sacrificial capping layer remains on the etch stop layer; and removing the sacrificial capping layer using wet etch chemistry.

20. The method of claim 19, wherein the forming a sacrificial capping layer comprises preferentially deposited on the top of each RMG stack by atomic layer deposition (ALD) using sequential exposures of titanium tetrakis(dimethylamido)titanium (TDMAT) and ozone (O₃) at a process pressure between about 1 Torr and about 3 Torr, a substrate temperature between about 100° C. and about 150° C., and a substrate rotation speed between about 10 RPM and about 50 RPM.
