

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12401093
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Yoon; Se Hyun et al.

Assembly manufacturing equipment and method for electrode assembly

Abstract

An electrode assembly manufacturing apparatus includes a stack table, a separator supply unit, first and second electrode supply units, and a side sealing device. A stack of a first electrode, a second electrode, and a separator between the first and the second electrode are stackable on the stack table. The separator supply unit is configured for supplying the separator to the stack table. The first electrode supply unit is configured for stacking the first electrode on a section of the separator on the stack table. The second electrode supply unit stacks the second electrode on a further section of the separator on the first electrode. A side sealing device heats at least one side surface of the stack.

Inventors: Yoon; Se Hyun (Daejeon, KR), Kwon; Chun Ho (Daejeon, KR), Kim; Beomsu (Daejeon, KR), Lee; Haksoo (Daejeon, KR), Jang; Hyeon Woo (Daejeon, KR), Kim; Yong Nam (Daejeon, KR), Park; Dong Hyeuk (Daejeon, KR)

Applicant: LG Energy Solution, Ltd. (Seoul, KR)

Family ID: 1000008779962

Assignee: LG Energy Solution, Ltd. (Seoul, KR)

Appl. No.: 18/650823

Filed: April 30, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20240283093 A1	Aug. 22, 2024

Foreign Application Priority Data

KR	10-2021-0090588	Jul. 09, 2021
KR	10-2021-0090589	Jul. 09, 2021

KR	10-2021-0090590	Jul. 09, 2021
KR	10-2021-0090591	Jul. 09, 2021
KR	10-2021-0090592	Jul. 09, 2021
KR	10-2021-0090596	Jul. 09, 2021
KR	10-2021-0090597	Jul. 09, 2021
KR	10-2021-0090598	Jul. 09, 2021
KR	10-2021-0090600	Jul. 09, 2021
KR	10-2021-0090601	Jul. 09, 2021

Related U.S. Application Data

continuation parent-doc US 17860688 20220708 PENDING child-doc US 18650823

Publication Classification

Int. Cl.: **B32B41/00** (20060101); **H01M4/04** (20060101); **H01M10/04** (20060101); **H01M10/0583** (20100101); **H01M50/46** (20210101); **H01M50/463** (20210101); **H01M50/466** (20210101); H01M10/0525 (20100101)

U.S. Cl.:

CPC **H01M50/46** (20210101); **H01M4/043** (20130101); **H01M4/0471** (20130101); **H01M10/0404** (20130101); **H01M10/0431** (20130101); **H01M10/045** (20130101); **H01M10/0459** (20130101); **H01M10/0468** (20130101); **H01M10/0583** (20130101); **H01M50/463** (20210101); **H01M50/466** (20210101); H01M10/0525 (20130101)

Field of Classification Search

CPC: H01M (50/46); H01M (4/043); H01M (4/0471); H01M (10/0404); H01M (10/0431); H01M (10/045); H01M (10/0459); H01M (10/0468); H01M (10/0525); H01M (10/0583); H01M (50/463); H01M (50/466); H01M (10/585); H01M (50/491); H01M (2004/021); Y02E (60/10); Y02P (70/50)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
9209491	12/2014	Kim et al.	N/A	N/A
9793535	12/2016	Yu et al.	N/A	N/A
10333126	12/2018	Joo et al.	N/A	N/A
10985356	12/2020	Joo et al.	N/A	N/A
2004/0180250	12/2003	Nanaumi et al.	N/A	N/A
2005/0186479	12/2004	Totsuka et al.	N/A	N/A
2006/0019154	12/2005	Imachi et al.	N/A	N/A
2007/0202394	12/2006	Viavattine	N/A	N/A
2008/0280208	12/2007	Naoi et al.	N/A	N/A
2009/0029259	12/2008	Okazaki et al.	N/A	N/A
2009/0136844	12/2008	Watanabe et al.	N/A	N/A

2010/0167176	12/2009	Kawai	N/A	N/A
2011/0052964	12/2010	Kim et al.	N/A	N/A
2011/0104550	12/2010	Ahn et al.	N/A	N/A
2013/0306237	12/2012	Nagasaka et al.	N/A	N/A
2014/0050958	12/2013	Kwon et al.	N/A	N/A
2014/0205879	12/2013	Jang et al.	N/A	N/A
2015/0033527	12/2014	Park et al.	N/A	N/A
2015/0162638	12/2014	Bernini et al.	N/A	N/A
2015/0180082	12/2014	Jung et al.	N/A	N/A
2015/0188108	12/2014	Miyazawa et al.	N/A	N/A
2016/0006072	12/2015	Cho et al.	N/A	N/A
2016/0028064	12/2015	Choi et al.	N/A	N/A
2016/0036087	12/2015	Na et al.	N/A	N/A
2016/0285062	12/2015	Jo et al.	N/A	N/A
2016/0380301	12/2015	Kosaka et al.	N/A	N/A
2017/0125794	12/2016	Zhao et al.	N/A	N/A
2018/0076424	12/2017	Kato	N/A	N/A
2018/0090787	12/2017	Makino et al.	N/A	N/A
2018/0102568	12/2017	Otohata	N/A	N/A
2018/0205109	12/2017	Cho et al.	N/A	N/A
2018/0226623	12/2017	Cho et al.	N/A	N/A
2018/0233725	12/2017	Yasuda et al.	N/A	N/A
2018/0233752	12/2017	Herrmann et al.	N/A	N/A
2018/0248219	12/2017	Kim et al.	N/A	N/A
2018/0294509	12/2017	Liu et al.	N/A	N/A
2018/0342722	12/2017	Zeng et al.	N/A	N/A
2019/0020009	12/2018	Watanabe et al.	N/A	N/A
2019/0044177	12/2018	Lee et al.	N/A	N/A
2019/0051924	12/2018	Kim et al.	N/A	N/A
2020/0006733	12/2019	Cho et al.	N/A	N/A
2020/0127334	12/2019	Pyo et al.	N/A	N/A
2020/0185753	12/2019	Kwon	N/A	N/A
2020/0227787	12/2019	Kang et al.	N/A	N/A
2020/0227788	12/2019	Chun et al.	N/A	N/A
2020/0235434	12/2019	Lee et al.	N/A	N/A
2020/0335813	12/2019	Oh et al.	N/A	N/A
2021/0050616	12/2020	Taguchi et al.	N/A	N/A
2021/0104775	12/2020	Ono et al.	N/A	N/A
2021/0351431	12/2020	Hwang	N/A	N/A
2022/0006161	12/2021	Kim et al.	N/A	N/A
2022/0029246	12/2021	Watanabe et al.	N/A	N/A
2022/0393225	12/2021	Kim et al.	N/A	N/A
2023/0006262	12/2022	Maruhashi et al.	N/A	N/A
2023/0028439	12/2022	Yoon	N/A	H01M 4/0471
2023/0036396	12/2022	Hosokawa et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
002763997	12/2005	CN	N/A
210403945	12/2019	CN	N/A

2856552	12/2015	EP	N/A
3905417	12/2020	EP	N/A
3985778	12/2021	EP	N/A
4027421	12/2021	EP	N/A
S45-005056	12/1969	JP	N/A
h02046663	12/1989	JP	N/A
H08138722	12/1995	JP	N/A
2002-208442	12/2001	JP	N/A
2002367628	12/2001	JP	N/A
2003-151615	12/2002	JP	N/A
2003201352	12/2002	JP	N/A
2005243455	12/2004	JP	N/A
2006032246	12/2005	JP	N/A
2008091192	12/2007	JP	N/A
2008282739	12/2007	JP	N/A
2009-218105	12/2008	JP	N/A
2009259719	12/2008	JP	N/A
2010199281	12/2009	JP	N/A
2012033275	12/2011	JP	N/A
2013149477	12/2012	JP	N/A
2013-254629	12/2012	JP	N/A
2015-141791	12/2014	JP	N/A
2015531989	12/2014	JP	N/A
2015532766	12/2014	JP	N/A
2016103425	12/2015	JP	N/A
2017-016946	12/2016	JP	N/A
2018-018712	12/2017	JP	N/A
2018-41703	12/2017	JP	N/A
2018510472	12/2017	JP	N/A
2018-532240	12/2017	JP	N/A
2018181843	12/2017	JP	N/A
2019153427	12/2018	JP	N/A
2019199028	12/2018	JP	N/A
2020145123	12/2019	JP	N/A
6844476	12/2020	JP	N/A
20080063523	12/2007	KR	N/A
20100051353	12/2009	KR	N/A
20110048132	12/2010	KR	N/A
101058786	12/2010	KR	N/A
101209010	12/2011	KR	N/A
20130132230	12/2012	KR	N/A
20140002718	12/2013	KR	N/A
20140022447	12/2013	KR	N/A
20140060797	12/2013	KR	N/A
20140062761	12/2013	KR	N/A
20140064405	12/2013	KR	N/A
20150016671	12/2014	KR	N/A
20150020667	12/2014	KR	N/A
20150022264	12/2014	KR	N/A
2015-0035079	12/2014	KR	N/A

20150034944	12/2014	KR	N/A
20150049892	12/2014	KR	N/A
20150050505	12/2014	KR	N/A
101531234	12/2014	KR	N/A
20150144183	12/2014	KR	N/A
101595621	12/2015	KR	N/A
20160054219	12/2015	KR	N/A
101643593	12/2015	KR	N/A
20160108116	12/2015	KR	N/A
101704759	12/2016	KR	N/A
101761720	12/2016	KR	N/A
101784033	12/2016	KR	N/A
2017-0124336	12/2016	KR	N/A
20180006324	12/2017	KR	N/A
101826894	12/2017	KR	N/A
101838350	12/2017	KR	N/A
20180037847	12/2017	KR	N/A
20180061872	12/2017	KR	N/A
20180128770	12/2017	KR	N/A
101941144	12/2018	KR	N/A
101963313	12/2018	KR	N/A
20190054491	12/2018	KR	N/A
20190056812	12/2018	KR	N/A
20190064977	12/2018	KR	N/A
101995038	12/2018	KR	N/A
102044363	12/2018	KR	N/A
20200023852	12/2019	KR	N/A
20200023853	12/2019	KR	N/A
20200023854	12/2019	KR	N/A
20200036641	12/2019	KR	N/A
20200061033	12/2019	KR	N/A
20200067575	12/2019	KR	N/A
20200069171	12/2019	KR	N/A
20200094325	12/2019	KR	N/A
20200095896	12/2019	KR	N/A
102164576	12/2019	KR	N/A
20200145375	12/2019	KR	N/A
20210033327	12/2020	KR	N/A
102253132	12/2020	KR	N/A
20210049297	12/2020	KR	N/A
20210051155	12/2020	KR	N/A
20210051164	12/2020	KR	N/A
2021-0074026	12/2020	KR	N/A
102256438	12/2020	KR	N/A
102265741	12/2020	KR	N/A
20210135861	12/2020	KR	N/A
2006120959	12/2005	WO	N/A
2016-152922	12/2015	WO	N/A
2017018456	12/2016	WO	N/A
2017/149991	12/2016	WO	N/A

2018116295	12/2017	WO	N/A
2019188719	12/2018	WO	N/A
2021/131879	12/2020	WO	N/A

OTHER PUBLICATIONS

International Search Report for Application No. PCT/KR2022/010001 mailed Nov. 8, 2022, pp. 1-3. cited by applicant

International Search Report for Application No. PCT/KR2022/010005 mailed Nov. 8, 2022, pp. 1-3. cited by applicant

International Search Report for Application No. PCT/KR2022/010006 mailed Nov. 4, 2022, pp. 1-3. cited by applicant

International Search Report for Application No. PCT/KR2022/010007 mailed Oct. 28, 2022, pp. 1-3. cited by applicant

International Search Report for Application No. PCT/KR2022/010008 mailed Nov. 4, 2022, pp. 1-3. cited by applicant

International Search Report for Application No. PCT/KR2022/010009 mailed Nov. 4, 2022, pp. 1-3. cited by applicant

International Search Report for Application No. PCT/KR2022/010010 mailed Oct. 28, 2022, pp. 1-3. cited by applicant

Notice of Preliminary Rejection for Korean Application No. 10-2022-0084662 dated Jan. 1, 2023. 8 pgs. cited by applicant

Written Opinion of the ISA for PCT/KR2022/010000 mailed Oct. 26, 2022. 4 pgs. cited by applicant

Written Opinion of the ISA for PCT/KR2022/010003 mailed Nov. 2, 2022. 3 pgs. cited by applicant

Written Opinion of the ISA for PCT/KR2022/010004 mailed Oct. 26, 2022. 4 pgs. cited by applicant

Extended European Search Report including Written Opinion for Application No. 22838071.3 dated Jun. 24, 2024, pp. 1-8. cited by applicant

Extended European Search Report for Application No. 22838066.3 dated Aug. 5, 2024, pp. 1-5. cited by applicant

Primary Examiner: Orlando; Michael N

Assistant Examiner: Rivera; Joshel

Attorney, Agent or Firm: Lerner David LLP

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) The present application is a continuation of U.S. patent application Ser. No. 17/860,688, filed on Jul. 8, 2022, which claims priority from Korean Patent Application No. 10-2021-0090590 filed on Jul. 9, 2021, Korean Patent Application No. 10-2021-0090596 filed on Jul. 9, 2021, Korean Patent Application No. 10-2021-0090588 filed on Jul. 9, 2021, Korean Patent Application No. 10-2021-0090589 filed on Jul. 9, 2021, Korean Patent Application No. 10-2021-0090591 filed on Jul. 9, 2021, Korean Patent Application No. 10-2021-0090592 filed on Jul. 9, 2021, Korean Patent Application No. 10-2021-0090597 filed on Jul. 9, 2021, Korean Patent Application No. 10-2021-0090598 filed on Jul. 9, 2021, Korean Patent Application No. 10-2021-0090600 filed on Jul. 9, 2021, and Korean Patent

TECHNICAL FIELD

(1) The present disclosure relates to an electrode assembly manufacturing device and a process for manufacturing an electrode assembly. More particularly, the present disclosure relates to an electrode assembly manufacturing device and process for manufacturing an electrode assembly for reducing the dimensions of a separator of an electrode assembly to increase an electrode density of the electrode assembly.

BACKGROUND

(2) Secondary batteries, unlike primary batteries, are rechargeable and have been widely researched and developed in recent years due to their small size and large capacity. As technology development and demand for mobile devices increase, the demand for secondary batteries as an energy source is rapidly increasing.

(3) The secondary battery is classified into a coin-type battery, a cylindrical battery, a prismatic battery, and a pouch-type battery according to a shape of a battery case. In a secondary battery, an electrode assembly mounted inside a battery case is a chargeable/dischargeable power generating element having a stacked structure of an electrode and a separator.

(4) The electrode assembly may be generally classified into a jelly-roll type in which a separator is interposed between a positive electrode and a negative electrode of a sheet type coated with an active material and wound, a stack type in which pluralities of positive and negative electrodes are sequentially stacked with a separator interposed therebetween, and a stack-and-folding type in which stacked unit cells are wound with a long-length separation film.

(5) In a process of manufacturing a stack-and-folding type electrode assembly in the related art, an electrode assembly was manufactured by heating and pressing a stack in which an electrode and a separator are stacked to bond the electrode and the separator. At this stage in the electrode assembly process, the separator is folded but the electrode is externally exposed.

(6) By heating and stacking the electrode and the separator in order to overcome certain deficiencies of conventional electrode assemblies, each layer is stacked and pressed so that the layers are bonded simultaneously with their stacking, and an outer portion of the separator is wrapped around the outermost portion of the stack of the electrode and the separator such that the stack is surrounded by the outer portion of the separator to thereby form an electrode assembly.

(7) However, in this electrode assembly, a space is formed between the side portion of the separator positioned on a side of the electrode assembly and a portion of the electrode on the side of the electrode assembly due to the separator surrounding the outermost portion of the stack, so that the side separator portion of the electrode assembly includes wrinkles. This configuration leads to an undesirable reduction in the energy density of the electrode assembly.

(8) Therefore, there is a need to address the space formed between the side portion of the separator and the portion of the electrode on the side of the electrode assembly.

SUMMARY OF THE DISCLOSURE

(9) The present disclosure provides for an electrode assembly manufacturing apparatus and a process for manufacturing an electrode assembly in which such apparatus and process may be configured for fabricating an electrode assembly in a condensed form relative to prior electrode assemblies. In particular, an electrode assembly may be condensed relative to prior electrode assemblies by heating and pressing a stack of a first electrode, a second electrode, and a separator between the first and the second electrodes to decrease a width of the electrode assembly.

(10) In one aspect, an electrode assembly manufacturing apparatus may include a stack table, a separator supply unit, a first electrode supply unit, a second electrode supply unit, and a side sealing device. A first electrode, a separator, and a second electrode may be stacked in a stack on the stack table in which the first electrode and the second electrode are disposed between sections

of a folded separator. The separator supply unit may be configured for supplying the separator to the stack table. The first electrode supply unit may be configured for supplying the first electrode to the stack table and may be further configured for stacking the first electrode over the stack table. The second electrode supply unit may be configured for supplying the second electrode over the stack table and may be further configured for stacking the second electrode over the stack table. The side sealing device may be configured for heating at least one side surface of the stack.

(11) In some arrangements, the side sealing device may include a pair of heating bars. The pair of heating bars may include heating surfaces that face towards each other. The pair of heating bars may be moved towards each other to compress the side surface or the side surfaces of the stack.

(12) In some arrangements, the electrode assembly manufacturing apparatus further may include a press unit. The press unit may be configured for compressing the stack and further may be configured for heating the stack. In some arrangements, the press unit may be configured to compress and to heat up the stack simultaneously. In some other arrangements, the press unit may be configured to heat up the stack prior to compressing the stack while in still other arrangements, the press unit may be configured to heat up the stack prior to and during the compressing of the stack.

(13) In some arrangements, the side sealing device may compress the stack in a direction perpendicular to a pressing direction of the press unit.

(14) In some arrangements, the press unit may include a pair of pressing blocks. The pair of pressing blocks may face each other. The pair of pressing blocks may be moved towards each other to compress opposing upper and lower surfaces of the stack.

(15) In some arrangements, each of the pair of pressing blocks may include a pressing surface. Each of the pressing surfaces may be configured for contacting opposing surfaces of the stack to compressing the stack such that the opposing surfaces of the stack define a plane.

(16) In some arrangements, the press unit may include a press heater configured for heating the pair of pressing blocks.

(17) In some arrangements, the pair of pressing blocks of the press unit may include a pressing surface that may define a plane. The pressing surface of the pressing block may have either one or both of a width that is longer than a width of the stack and a length that is longer than a length of the stack.

(18) In some arrangements, the first electrode supply unit may include a first electrode seating table and a first transfer head. The first electrode may be seated on the first electrode seating table before being stacked on the stack table. The first transfer head may be configured for temporary fixation of the first electrode such as when the first electrode is seated on the first electrode seating table and may be further configured for picking and placing of the first electrode in a stack on the stack table. In some such arrangements, the first transfer head may be a first suction head which may be configured for suctioning the first electrode to fix the first electrode to the first transfer head. In some such arrangements, the first suction head may include a vacuum device to provide the suctioning. In some arrangements, the second electrode supply unit may include a second electrode seating table and a second transfer head. The second electrode may be seated on the second electrode seating table before being stacked in a stack on the stack table. The second transfer head may be configured for temporary fixation of the second electrode such as when the second electrode is seated on the second electrode seating table. In some such arrangements, the second transfer head may be a second suction head which may be configured for suctioning the second electrode to fix the second electrode to the second transfer head. In some such arrangements, the second suction head may include a vacuum device to provide the suctioning.

(19) In some arrangements, the electrode assembly manufacturing apparatus further may include a rotating unit for rotating the stack table. The first electrode supply unit may be located on one side of the rotating unit, and the second electrode supply unit may be located on the other side of the rotating unit. The rotating unit may rotate the stack table such that the top surface of the stack table

faces towards the first transfer head when the first electrode is stacked in the stack. The rotating unit may rotate the stack table such that the top surface of the stack table faces the second transfer head when the second electrode is stacked in the stack.

(20) In some arrangements, the rotating unit may alternately rotate the stack table in a direction of the first electrode supply unit and a direction of the second electrode supply unit.

(21) In another aspect, an electrode assembly is manufactured by a process. During a stacking operation of this process, a first electrode, a separator, and a second electrode may be stacked to form a stack. In some arrangements of this process, the first electrode and the second electrode may be alternately disposed between sections of the separator. The sections of the separator are formed by folding the separator in a zigzag manner. During a side sealing operation of this process, at least one side surface of the stack may be heated and thereby bond the first electrode, the separator, and the second electrode to a portion of the separator extending along the side surface of the stack.

(22) In some arrangements of the process, during the side sealing operation, the side surface or the side surfaces of the stack may be compressed at a temperature of 100° C. to 200° C. for a time of 10 seconds or less.

(23) In some arrangements of the process, the stack may be compressed along a direction the stack is stacked. In some such arrangements, the stack may be heated up. The stack may be heated up prior to, simultaneously with, or both prior to and simultaneously with the stack being compressed. In some arrangements, the press unit may be configured to compress and to heat up the stack simultaneously. In some other arrangements, the press unit may be configured to heat up the stack prior to compressing the stack while in still other arrangements, the press unit may be configured to heat up the stack prior to and during the compressing of the stack.

(24) In some arrangements of the process, during the side sealing operation, the side surface or the side surfaces of the stack may be compressed at a pressure in a range from 0.1 MPa to 1.5 MPa.

(25) In accordance with the electrode assembly manufacturing apparatus and the electrode assembly manufacturing process according to the present disclosure, it is to be understood that an electrode density and thereby an energy density of the electrode assembly may be increased over electrode assemblies known in the relevant art by condensing the electrode assembly. In some arrangements, a width of a stack of stacked components of the electrode assembly may be decreased in condensing the electrode assembly. In some such arrangements, the width of the stack may be decreased by heating and pressing the stack in which the stack may include first and second electrodes and a separator between the first and the second electrodes.

(26) In some arrangements according to any of the foregoing, the electrode assembly may be manufactured with dimensions corresponding to an inner space of a pouch, e.g., for use in a pouch-type battery or an inner space of a can, e.g., for use in a cylindrical battery, in which the electrode assembly may be accommodated. In this manner, the size of the pouch or the can may be easily changed as desired without concern for the ability to fabricate the electrode assembly.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 is a cross-sectional elevation view illustrating an electrode assembly according to an exemplary embodiment;

(2) FIG. 2 is a perspective view illustrating a stack of the electrode assembly of FIG. 1;

(3) FIG. 3 is a plan view illustrating an electrode assembly manufacturing apparatus according to an exemplary embodiment;

(4) FIG. 4 is an elevation view illustrating the electrode assembly manufacturing apparatus of FIG. 3;

(5) FIG. 5 is a cross-sectional view illustrating an electrode assembly within a side sealing device

of the electrode assembly manufacturing apparatus of FIG. 3 according to an exemplary embodiment; and

(6) FIG. 6 is a process flow diagram of an electrode assembly manufacturing process according to an exemplary embodiment.

(7) FIG. 7 is a pair of photographs of enlarged cross sections of an electrode assembly at approximately the location along lines A-A' of the electrode assembly according to FIG. 1 taken under an optical microscope;

(8) FIG. 8 is a pair of photographs of enlarged cross-sections of an electrode assembly taken with an optical microscope after cutting the cross-sections of Comparative Examples 1 and 2 as described further herein; and

(9) FIG. 9 is a set of photographs of an electrode assembly according to Comparative Example 3.

DETAILED DESCRIPTION

(10) Where the specification states that a part “includes” a certain element or that a specific structure or shape is “characterized,” unless otherwise stated, such terms do not mean that other components or other structures and shapes are excluded, and indeed other components, structures, and shapes may be included.

(11) Since the arrangements described herein may be variously transformed, specific arrangements are presented and described in detail in the detailed description. However, the disclosure of such arrangements is not intended to limit the content of the invention according to those arrangements and should be understood to include all transformations, equivalents, and substitutes included in the spirit and scope of the present disclosure.

(12) Hereinafter, examples of the present invention will be described in detail with reference to the drawings. However, the drawings are for illustrative purposes only, and the scope of the present invention is not limited or intended to be limited by the drawings.

(13) Referring now to FIGS. 1 and 2, an electrode assembly **10** may include a stack **S** and a second separator **5** that may surround the stack **S**.

(14) As shown, in the stack **S**, a first electrode **1** and a second electrode **2** may be alternately disposed between spacer sections **4a** of first separator **4**. As further shown, first separator **4** may be folded in a zigzag manner to form the spacer sections **4a**.

(15) Referring to FIGS. 3-5, the electrode assembly manufacturing apparatus **100** includes a stack table **10**, a separator supply unit **20**, a first electrode supply unit **30**, a second electrode supply unit **40**, and a side sealing device **60**.

(16) The stack table **10** has one support surface on which a first combination of a first electrode **1**, a first section of a separator **4**, and a second electrode **2** are stacked in that order. A stacked stack **S** of further first electrodes **1**, second electrodes **2**, and additional sections of separator **4** placed between the first and the second electrodes is mounted on the first combination of the first electrode **1**, the first section of the separator **4**, and the second electrode **2**. The separator **4** is folded in a zigzag manner to form the sections of the separator **4** and corresponding folds of the separator on opposite sides of each of the sections of the separator. In this manner, each section of the separator **4** is disposed between respective ones of the first electrodes **1** and respective ones of the second electrodes **2** within the stack **S**.

(17) The stack table **10** is rotatable in one direction towards each first electrode **1** being supplied to allow the first electrode to be stacked on a respective section of the separator **4** supported by the stack table **10** and each prior stacked electrode and separator section, if any, and is rotatable in another direction opposite the one direction towards each second electrode **2** being supplied to allow the second electrode to be stacked on a respective section of the separator **4** supported by the stack table **10** and each prior stacked electrode and separator section. Accordingly, the electrode assembly manufacturing apparatus **100** may further include a rotating unit (not illustrated) for rotating the stack table **10**. For more information regarding such a rotating unit, see Korean Patent Application Publication No. 10-2020-0023853, the entire contents of which are incorporated herein

by reference.

(18) In the electrode assembly manufacturing apparatus **100**, the first electrode supply unit **30** is located on one side of the stack table **10**, and the second electrode supply unit **40** may be located on the other side of the stack table. In the configuration of manufacturing apparatus **100** shown, the rotating unit may alternately rotate the stack table **10** in the direction of the first electrode supply unit **30** and the direction of the second electrode supply unit **40**.

(19) For example, the separator supply unit **20** may be located above the stack table **10**, that is, along the stacking direction of the stack **S**. In this configuration, the first electrode supply unit **30** may be located at the left side of the stack table **10**, and the second electrode supply unit **40** may be located on the right side of the stack table based on the stacking direction of the stack **S**.

(20) In the configuration of manufacturing apparatus **100** shown, the rotating unit may rotate the stack table **10** so that the stack table faces a first transfer head **32**, or other first attachment device for temporarily holding the first electrode **1**, when stacking the first electrode **1**. The rotating unit may rotate the stack table so that the stack table faces a second transfer head **42**, or other second attachment device for temporarily holding the second electrode **2**, when stacking the second electrode **2**.

(21) In using the electrode assembly manufacturing apparatus **100**, a section of the separator **4** is supplied by the separator supply unit **20** and placed, and in some arrangements, mounted, onto the stack table **10**. When the rotating unit rotates the stack table to the left, the first electrode **1** may be supplied from the first electrode supply unit **30** onto the supplied section of the separator **4**. In addition, the rotating unit may rotate the stack table **10** to the right, in which such rotation may occur at the same time as the separator **4** is supplied. In this rotational configuration of the rotating unit, the separator **4** may form a first pocket in the form of a left pocket covering a lower surface, a right surface, and an upper surface of the first electrode **1** that is the first electrode of stack **S** placed over stack table **10** in which the upper surface of the first electrode may be covered by a section of the separator. In this configuration, the second electrode **2** may be supplied from the second electrode supply unit **40** and onto the section of the separator covering the upper surface of the first electrode **1**.

(22) When the above process is repeated, the separator **4** may be provided from the separator supply unit **20** to overlie the stack table **10** in the forms of left pockets and right pockets oppositely configured to the left pockets. In such configurations, the left and the right pockets form alternating respective left and right openings as each section of the separator **4** is placed to overlie the stack table **10** in which such left and right openings are configured to receive the first electrodes **1** and the second electrodes **2**, supplied by the first electrode supply unit **30** and the second electrode supply unit **40**, respectively. Further, side sections **4a** of the separator **4**, which may be in the form of folded parts when the separator **4** is folded (See FIG. 2), may be provided at positions facing the left and right openings. In some alternative arrangements, which may be a mirror arrangement to the arrangement of electrode assembly manufacturing apparatus **100**, the separator **4** may form a first pocket in the form of a right pocket covering a lower surface, a left surface, and an upper surface of the second electrode **2**. In such a mirror arrangement, the second electrode **2** may be the first electrode of stack **S** placed over stack table **10**.

(23) The stack table **10** may further include a table body (not illustrated) which determines a shape of the stack table **10** and a table heater (not illustrated), which for example may be a resistor coil on, under, or embedded within the table body. The table heater may heat up the table body and thereby heat up the stack **S** resting on the stack table **10**.

(24) The table heater may heat up the stack **S** prior to the stack **S** being heated and compressed by a first press unit **50** of the electrode assembly manufacturing apparatus **100**. This pre-heating of the stack **S** by the table heater may reduce the press time needed for sufficient pressing by the first press unit **50** by shortening the time for heat conduction to the center of the stack **S**.

(25) The first electrode **1** may be configured as a positive electrode, and the second electrode **2** may

be configured as a negative electrode, but the electrode assembly manufacturing apparatus in accordance with the present disclosure is not limited to such a configuration, and for example, of course, the first electrode 1 may be configured as a negative electrode and the second electrode 2 may be configured as a positive electrode.

(26) In some arrangements, the positive electrode may be manufactured by, for example, coating a positive electrode current collector with a positive electrode coating mixture comprising a positive electrode active material, a conductive material, and a binder and then drying the coating mixture. If necessary, a filler may be added to the mixture. Such materials may be any appropriate materials used in the relevant field, in particular those commonly used for the particular application.

(27) For example, the positive electrode active material may include: layered compounds, such as lithium cobalt oxide (LiCoO_2) and lithium nickel oxide (LiNiO_2), or compounds substituted with one or more transition metals; lithium manganese oxides represented by the chemical formula $\text{Li}_{1-x}\text{Mn}_2\text{O}_4$ (where x is 0 to 0.33), such as LiMnO_2 , LiMn_2O_3 , and LiMnO_2 ; lithium copper oxide (Li_2CuO_2); vanadium oxides, such as LiV_3O_8 , LiFe_3O_4 , V_2O_5 , and $\text{Cu}_2\text{V}_2\text{O}_7$; nickel (Ni) site-type lithium nickel oxides represented by the chemical formula $\text{LiNi}_{1-x}\text{M}_x\text{O}_2$ (wherein M=Co, Mn, Al, Cu, Fe, Mg, B, or Ga, and x=0.01 to 0.3); lithium manganese composite oxides represented by the chemical formula $\text{LiMn}_2\text{O}_2\text{M}_x\text{O}_2$ (where M=Co, Ni, Fe, Cr, Zn, or Ta, and x=0.01 to 0.1) or $\text{Li}_2\text{Mn}_3\text{MO}_8$ (where M=Fe, Co, Ni, Cu, or Zn); LiMn_2O_4 in which a part of Li in the formula is substituted with an alkaline earth metal ion; disulfide compounds; and $\text{Fe}_2(\text{MoO}_4)_3$, but the positive electrode active material is not limited to such materials.

(28) The materials that may be used for the positive electrode current collector are not particularly limited. The positive electrode current collector preferably has a relatively high conductivity without causing a chemical change when used in a battery. For example, stainless steel; aluminum; nickel; titanium; calcined carbon; or a material in which a surface of aluminum or stainless steel is treated with carbon, nickel, titanium, silver, and the like may be used. Preferably, the positive electrode current collector may be aluminum. Adhesion between the current collector and the positive electrode coating mixture desirably may be increased by including fine irregularities on a surface of the current collector interfacing with the coating mixture. Moreover, various structural configurations of the positive electrode current collector may be used, such as a film, a sheet, a foil, a net, a porous body, a foam body, and a non-woven body. The positive electrode current collector generally may have a thickness in a range from 3 μm to 500 μm .

(29) The conductive material in the positive electrode coating mixture generally may be included in an amount from 1 to 50 wt % of the total weight of the mixture including the positive electrode active material. The conductive material is not particularly limited and preferably has a relatively high conductivity without causing a chemical change when used in a battery. For example, graphite, such as natural graphite and artificial graphite; carbon black, such as carbon black, acetylene black, Ketjen black, channel black, furnace black, lamp black, and summer black; conductive fibers, such as carbon fibers and metal fibers; carbon and metal powders, such as carbon fluoride, aluminum, and nickel powders; conductive whiskers, such as zinc oxide and potassium titanate; conductive metal oxides, such as titanium oxide; and polyphenylene derivatives may be used for the conductive material.

(30) The binder in the positive electrode coating mixture assists in bonding between the active material and the conductive material and in bonding the coating mixture to the current collector. Such a binder is generally included in an amount from 1 to 50% by weight of the total weight of the mixture including the positive electrode active material. Examples of the binder may include polyvinylidene fluoride, polyvinyl alcohol, carboxymethylcellulose (CMC), starch, hydroxypropylcellulose, regenerated cellulose, polyvinylpyrrolidone, tetrafluoroethylene,

polyethylene, polypropylene, ethylene-propylene-diene terpolymer (EPDM), sulfonated EPDM, styrene butylene rubber, fluororubber, and various copolymers.

(31) The filler optionally added to the positive electrode coating mixture may be used as a component to suppress the expansion of the positive electrode. Such a filler is not particularly limited and may include a fibrous material that does not cause a chemical change when used in a battery. For example, olefin polymers, such as polyethylene and a polypropylene, and fibrous materials, such as glass fiber and carbon fiber, may be used.

(32) In some arrangements, the negative electrode may be manufactured by coating, drying, and pressing a negative electrode active material on a negative electrode current collector, and, if necessary, the conductive materials, binders, fillers, and the like discussed above may be optionally further included. In any event, any appropriate materials used in the relevant field may be used, in particular those commonly used for the particular application. For example, as the negative electrode active material, carbon, such as non-graphitizable carbon and graphitic carbon; metal composite oxides represented by the chemical formulas $\text{Li}_{0.5}\text{Fe}_{0.5}\text{O}_{1.5}$ ($0 \leq x \leq 1$), $\text{Li}_{0.5}\text{WO}_{1.5}$ ($0 \leq x \leq 1$), $\text{Sn}_{0.5}\text{Me}_{0.5}\text{O}_2$ (Me : Mn, Fe, Pb, Ge; Me' : Al, B, P, Si, elements of groups 1, 2 and 3 of the periodic table, and halogens; $0 < x \leq 1$; $1 \leq y \leq 3$; $1 \leq z \leq 8$); lithium metal; lithium alloys; silicon-based alloys; tin-based alloys; metal oxides, such as SnO , SnO_2 , PbO , PbO_2 , Pb_2O_3 , Pb_3O_4 , Sb_2O_3 , Sb_2O_4 , Sb_2O_5 , GeO , GeO_2 , Bi_2O_3 , Bi_2O_4 , and Bi_2O_5 ; conductive polymers, such as polyacetylene; and Li—Co—Ni-based materials may be used.

(33) The materials that may be used for the negative electrode current collector are not particularly limited. The negative electrode current collector preferably has a relatively high conductivity without causing a chemical change when used in a battery. For example, copper; stainless steel; aluminum; nickel; titanium; calcined carbon; a material in which a surface of copper or stainless steel is surface-treated with carbon, nickel, titanium, silver, and the like; and an aluminum-cadmium alloy may be used.

(34) In addition, like the positive electrode current collector, the bond between the negative electrode current collector and the negative electrode active material may be strengthened by forming fine irregularities on the surface of the negative electrode current collector. Various structural configurations of the negative electrode current collector may also be used such as a film, a sheet, a foil, a net, a porous body, a foam body, a non-woven body, and the like. In addition, the negative electrode current collector may have a thickness generally in a range of 3 μm to 500 μm .

(35) In some arrangements, the separator may be an organic/inorganic complex porous SRS (Safety-Reinforcing Separator). The SRS may have a structure in which a coating layer component including inorganic particles and a binder polymer is coated on a polyolefin-based separator substrate.

(36) Since the SRS does not undergo high-temperature thermal contraction due to the heat resistance of the component inorganic particles, even if the electrode assembly is penetrated by a needle-shaped conductor, an elongated length of the safety separator can be maintained.

(37) The SRS may have a uniform porous structure formed by an interstitial volume between the inorganic particles that are components of the coating layer, in addition to the porous structure of the separator substrate itself. The pores may not only significantly alleviate any external impacts applied to the electrode assembly but may also facilitate the movement of lithium ions through the pores, as well as enable a large amount of electrolyte to be impregnated into the separator, thereby promoting improved performance of the battery.

(38) In some arrangements, the separator may be dimensioned in its width dimension (orthogonal to the longitudinal dimension in which the separator is unrolled) such that separator portions extend outwardly on both sides beyond corresponding edges of adjacent positive and negative electrodes (hereinafter “surplus portions”). Moreover, such outwardly extending portions of the separator may have a structure including a coating layer thicker than a thickness of the separator formed on one or

both sides of the separator in order to prevent shrinkage of the separator. For more information regarding the thicker coating layer on the outwardly extending surplus portions of the separator, see Korean Patent Application Publication No. 10-2016-0054219, the entire contents of which are incorporated herein by reference. In some arrangements, each separator surplus portion may have a size of 5% to 12% of the width of the separator. Moreover, in some arrangements, the coating layer may be coated on both surfaces of the separator over a width of 50% to 90% of the width of each separator surplus portion. In addition, the widths of the coating layers may be the same or different on each surface of the separator.

(39) In some arrangements, the coating layer may include inorganic particles and a binder polymer as components.

(40) In some arrangements, examples of the polyolefin-based separator component may include high-density polyethylene, linear low-density polyethylene, low-density polyethylene, ultra-high molecular weight polyethylene, polypropylene, or derivatives thereof.

(41) In some arrangements, the thickness of the coating layer may be smaller than the thickness of the first electrode or the second electrode. In some such arrangements, the thickness of the coating layer may be 30% to 99% of the thickness of the first electrode or the second electrode.

(42) In some arrangements, the coating layer may be formed by wet coating or dry coating.

(43) In some arrangements, the polyolefin-based separator substrate and the coating layer may exist in a form in which pores on the surface of the substrate and the coating layer are anchored with each other, whereby the separator substrate and the coating layer may be bonded together firmly. The substrate and the coating layer of the separator may have a thickness ratio from 9:1 to 1:9. A preferred thickness ratio may be 5:5.

(44) In some arrangements, the inorganic particles may be inorganic particles commonly used in the art. The inorganic particles may interact with each other to form micropores in the form of empty spaces between the inorganic particles while structurally helping to maintain the physical shape of the coating layer. In addition, since the inorganic particles generally have properties that do not change their physical properties even at high temperatures of 200° C. or more, the resultant organic/inorganic complex porous film generally and desirably has excellent heat resistance.

(45) In addition, the materials that may be used for the inorganic particles are not particularly limited but are preferably electrochemically stable. That is, the inorganic particles are preferably selected such that oxidation and/or reduction reactions do not occur in the operating voltage range of the applied battery (for example, 0 to 5 V based on Li/Li⁺). In particular, the use of inorganic particles having ion transport ability may improve performance by increasing the ionic conductivity in the electrochemical device. Thus, use of inorganic particles having ionic conductivity as high as possible is preferable. In addition, when the inorganic particles have a high density, it is difficult to disperse the inorganic particles during coating, and it can also undesirably increase the weight of the battery. Therefore, use of inorganic particles having density as low as possible is preferable. In addition, inorganic materials having a high dielectric constant contribute to an increase in the degree of dissociation of electrolyte salt, such as a lithium salt, in a liquid electrolyte, thereby improving the ionic conductivity of the electrolyte.

(46) For the above reasons, the inorganic particles may be at least one type selected from the group consisting of inorganic particles having piezoelectricity and inorganic particles having lithium-ion transport ability.

(47) Inorganic particles having piezoelectricity refer to materials which are a nonconductor at normal pressure but have a property of conducting electricity due to a change in the internal structure when a certain pressure is applied. They are also materials which exhibit high permittivity characteristics with a permittivity constant of 100 or more. Inorganic particles having piezoelectricity also generate an electric potential difference between opposing surfaces, e.g., of a separator, by causing one surface to be positively charged and the other surface to be negatively charged, or vice versa, when either tension or compression is applied to an object composed of the

inorganic particles, e.g., a separator.

(48) When the inorganic particles having the above characteristics are used as a coating layer component, in the case of an internal short circuit of both electrodes due to an external impact, such as by a needle-shaped conductor, the positive electrode and the negative electrode may not directly contact one another due to the inorganic particles coated on the separator. Moreover, due to the piezoelectricity of the inorganic particles, an electric potential difference may occur within the particles, which desirably may result in electron movement between both electrodes (i.e., the flow of a minute current), so that it may be possible to gently reduce the voltage of the battery, thereby improving safety.

(49) Examples of materials for the inorganic particles having piezoelectricity may be one or more selected from the group consisting of BaTiO_3 , $\text{Pb}(\text{Zr,Ti})\text{O}_3$ (PZT), those represented by the chemical formula $\text{Pb}_{1-x}\text{La}_x\text{Zr}_{1-y}\text{Ti}_y\text{O}_3$ (PLZT), $\text{Pb}(\text{Mg}_{0.3}\text{Nb}_{0.2/3})\text{O}_3$ — PbTiO_3 (PMN-PT), and hafnia (HfO_2), but are not limited to these materials.

(50) Inorganic particles having lithium-ion transport ability refer to inorganic particles containing a lithium element but not storing lithium and instead having a function of moving lithium ions. The inorganic particles having lithium-ion transport ability are capable of transporting and moving lithium ions due to a kind of defect in the particle structure. As a result, the lithium-ion conductivity in the battery may be improved, thereby improving battery performance.

(51) Examples of materials for the inorganic particles having lithium-ion transport ability may be one or more selected from the group consisting of lithium phosphate (Li_3PO_4), lithium titanium phosphate (represented by the chemical formula $\text{Li}_x\text{Ti}_y(\text{PO}_4)_3$, wherein $0 \leq x < 2$, $0 < y < 3$), lithium aluminum titanium phosphate (represented by the chemical formula $\text{Li}_x\text{Al}_y\text{Ti}_z(\text{PO}_4)_3$, wherein $0 < x < 2$, $0 < y < 1$, $0 < z < 3$), glass of the series represented by the chemical formula $(\text{LiAlTiP})_x\text{O}_y$ ($0 < x < 4$, $0 < y < 13$), lithium lanthanum titanate (represented by the chemical formula $\text{Li}_x\text{La}_y\text{TiO}_3$, wherein $0 < x < 2$, $0 < y < 3$), lithium germanium thiophosphate (represented by the chemical formula $\text{Li}_x\text{Ge}_y\text{P}_z\text{S}_w$, wherein $0 < x < 4$, $0 < y < 1$, $0 < z < 1$, $0 < w < 5$), lithium nitride (represented by the chemical formula Li_xN_y , wherein $0 < x < 4$, $0 < y < 2$), glass of the SiS_2 series (represented by the chemical formula $\text{Li}_x\text{Si}_y\text{S}_z$, wherein $0 < x < 3$, $0 < y < 2$, $0 < z < 4$), and glass of the P_2S_5 series (represented by the chemical formula $\text{Li}_x\text{P}_y\text{S}_z$, wherein $0 < x < 3$, $0 < y < 3$, $0 < z < 7$), but are not limited to these materials.

(52) The composition ratio of the inorganic particles and the binder polymer, which are components of the coating layer of the separator, is not particularly limited, but may be adjusted within the range of 10:90 to 99:1 by weight %, and preferably within the range of 80:20 to 99:1 by weight %. When the composition ratio is less than 10:90 by weight %, the content of the polymer may become excessively large, and the pore size and porosity may be reduced due to a decrease in the empty space formed between the inorganic particles, finally resulting in deterioration of the battery performance. On the other hand, when the composition ratio exceeds 99:1 by weight %, the content of the polymer may be too small and the mechanical properties of the final organic/inorganic composite porous separator may become deteriorated due to weakened adhesive force between the inorganic materials.

(53) In some arrangements, a binder polymer commonly used in the art may be used as the binder polymer.

(54) The coating layer of the organic/inorganic composite porous separator may further include other commonly known additives in addition to the aforementioned inorganic particles and binder polymer.

(55) In some arrangements, the coating layer may be referred to as an active layer.

(56) Referring again to FIGS. 1 and 2, the first separator 4 may include a plurality of spacer sections 4a each positioned between the first electrode 1 and the second electrode 2 and side

sections **4b** each connected to and extending between sides of adjacent ones of the spacer sections **4a**. As used herein, the side of the spacer section **4a** refers to one side in a direction perpendicular to a stacking direction of the stack **S**. Accordingly, the side of the spacer section **4a** is a position corresponding to the side of the stack **S**.

(57) In the stack **S**, the side sections **4b** may be alternately positioned on the side surfaces of respective layers of the stack. Adjacent spacer sections **4a** and the side section **4b** attached to such adjacent spacer sections **4a** form an opening of the first separator **4a** such that the side surfaces of the stack opposite the side sections **4b** are defined by the first and the second electrodes received in the opening of the first separator. As such, the stack **S** may be alternately provided with the side sections **4b** and the openings defined by the separator **4** on a pair of opposite side surfaces for each layer of the stack.

(58) The first electrode **1** and the second electrode **2** may not be disposed in or on the side sections **4b**.

(59) As shown in the example of FIG. **1**, the second separator **5** may be positioned on an upper surface, a lower surface, and at least one pair of opposing side surfaces of the stack **S**. That is, an end of the second separator **5** may be connected to an end of the first separator **4** and wound around the stack **S** at least once, as further shown in FIG. **1**.

(60) Accordingly, an inner separator surface of the second separator **5** positioned on a pair of opposing side surfaces of the stack **S** may face the side sections **4b**. Additionally, the second separator **5** positioned on at least one pair of opposite side surfaces of the stack **S** may be in contact with at least one or more side sections **4b**.

(61) The electrode assembly **10** may be manufactured by heating or heating and compressing the side of the stack **S** when the second separator **5** is wound around and onto an outermost portion of the stack. For example, the electrode assembly **10** may be manufactured by heating or heating and compressing, by a side sealing device **60** (see FIG. **3** and related description further herein) including a pair of pressing blocks **60a** and **60b**, opposite side surfaces of the stack **S** when the second separator **5** is wound around and onto the outermost portion of the stack. Spaces formed between the side sections **4b** positioned on both side surfaces of the stack **S** and the inner separator surface of the second separator **5** facing the side sections **4b** may be condensed by thermally fusing one or more of the side sections and the inner separator surface. Such thermal fusion bonding of the side sections **4b** and the second separator **5** may be achieved by heating and compressing the opposing side surfaces of the stack with the side sealing device **60** while the second separator **5** is wound on the outermost region of the stack **S**.

(62) The electrode assembly **10** may be manufactured by heating and compressing any or all of an upper surface, a lower surface, and opposing side surfaces of a stack **s** in which a second separator **5** is wound around and onto the outermost portion of the stack. For example, the electrode assembly **10** may be manufactured by heating and compressing the upper surface and the lower surface of the stack **S** with a press unit **50** (see FIG. **3** and related description further herein) and, either separately or at the same time, heating and compressing the opposite side surfaces of the stack **S** with the side sealing device **60**.

(63) The press unit **50** may include a pair of heated pressing blocks **50a** and **50b**. Spaces between the first electrode **1**, the first separator **4**, and the second electrode **2** may be condensed by thermally fusing the upper and lower surfaces of the stack **S** to the inner separator surface of the second separator **5**. Such thermal fusion bonding of the upper and lower surfaces with the second separator **5** may be achieved by heating and compressing the stack **S** with the pair of pressing blocks **50a** and **50b** while the second separator **5** is wound on the outermost region of the stack **S**. Here, the upper and lower surfaces of the stack **S** refer to the outer surfaces of the stack **S** positioned at the upper side and the lower side in the stacking direction.

(64) Accordingly, in the example of electrode assembly **10**, the first electrode **1** and the first separator **4** and the first separator **4** and the second electrode **2** may be bonded to each other. In

addition, as the upper and lower surfaces of the stack S are heated up and compressed, the side sections **4b** may be compressed and adjacent ones of the side sections **4b** may become thermally fused to each other. That is, two or more side sections **4b** may be bonded to each other. In that regard, unlike the schematic representation illustrated in FIG. 1, the side sections **4b** may extend outwardly past the ends of the electrodes **1**, **2** by a relatively significant distance, as shown in the examples of FIGS. 5 and 6. In that manner, the side sections **4b** can be deflected towards one another via any one or any combination of heating and compressing of the side sealing device **60** and press unit **50** and thereby bonded to each other.

(65) In some arrangements, two or more bonded side sections **4b** of the first separator **4** and the inner separator surface of the second separator **5** positioned so as to face the side sections **4b** of the stack S may be bonded to each other.

(66) In some arrangements, the side sections **4b** may be bonded to the inner separator surface of the second separator **5** in a state in which adjacent ones of the side sections **4b** are not bonded to each other. In that instance, a side section **4b** may be bonded to the second separator **5** in a folded state without being bent in a direction parallel to the stacking direction of the stack S, or a side section **4b** may be bent one or more times in either direction parallel to the stacking direction of the stack S while being bonded to the second separator **5**.

(67) A length of each side section **4b** may be in a range from 0.1% to 1% based on 100% of the total length of the spacer section **4a** to which the respective side section is attached. In that instance, the length of the side section **4b** may refer a state in which the side section **4b** is not bent.

(68) If a length of a side section **4b** exceeds 1% of the total length of the spacer section **4a** to which the side section is attached, then the electrode density and energy density of the electrode assembly **10** may be reduced. Here, the total length of the spacer section **4a** refers to the length from the side section **4b** to the opening opposite the side section **4b**.

(69) In addition, the number of side sections **4b** that are bonded to the inner separator surface of the second separator **5** may be 30% or more of the total number of side sections **4b**. Preferably, the number of side sections **4b** may be 40% or more, and more preferably, 50% or more.

(70) Any side section **4b** may be bonded to the inner separator surface of the second separator **5** in a state in which a plurality of adjacent side sections **4b** are bonded to each other. An area of the second separator **5** that is bonded to any of the side sections **4b** when adjacent ones of the side sections **4b** of the first separator **4** are bonded to each other may be 30% or more of the total area of the second separator **5** positioned on one pair of opposite side surfaces of the stack S. Preferably, such area of the second separator **5** may be 40% or more, and more preferably, 50% or more.

(71) In the electrode assemblies **10** in which the number of bonded side sections **4b** and the bonding area between the side sections **4b** and the second separator **5** are less than the foregoing 30% thresholds, a side surface of the stack S may have side sections **4b** that are not sufficiently fixed. In this instance, it may not be easy to insert the electrode assembly **10** into a pouch or a can. Further, in the electrode assemblies **10** in which the number of bonded side sections **4b** and the area of the second separator **5** do satisfy the foregoing 30% thresholds, the side section **4b** may protrude from the sealed portion of a pouch, the electrode assembly may undesirably be sealed together with the pouch.

(72) In addition, there are limits in minimizing the size of the pouch or the can because the difference between the size of the pouch or the can and the size of the electrode increases.

(73) In some arrangements, when adjacent side sections **4b** are bonded to each other, 50% or more of the total number of the side sections **4b** may be bonded to each other. In some arrangements, widths of the first electrode **1** and the second electrode **2** may be provided to be smaller than the width of the stack S. In other words, the electrode assembly **10** may be positioned so that a side section **4b** and the ends of the first electrode **1** and the second electrode **2** in layers adjacent to a layer of such side section **4b** are not overlying or underlying each other. In that instance, the first electrode **1** or the second electrode **2** is not positioned between the adjacent side sections **4b** such

that the adjacent side sections **4b** may be bonded to each other.

(74) For example, when 10 side sections **4b** are included in the electrode assembly **10** and 50% of the total number of side sections **4b** are bonded to each other, the electrode assembly **10** may include a set of two of the side sections **4b** that are bonded to each other, a set of three of the side sections **4b** that are bonded to each other, and a set of five side sections **4b** which are not bonded to their adjacent side sections **4b**.

(75) Referring again to FIGS. **3** and **4**, as in the example of the electrode assembly manufacturing apparatus **100**, separator supply unit **20** may be configured for supplying the separator **4** to the stack table **10**. For more information regarding such a separator supply unit, see Korean Patent Application Publication No. 10-2020-0023853. For example, as shown in FIG. **4**, the separator supply unit **20** may be located above the stack table **10**. In addition, the separator supply unit **20** may include a separator roll **21** on which the separator **4** may be wound. The separator **4** wound on the separator roll **21** may be supplied to the stack table **10** by gravity while being gradually loosened.

(76) The separator supply unit **20** is formed with a passage through which the separator **4** passes. The separator supply unit **20** may include a separator heating unit (not illustrated) for heating the passing separator **4**. For more information regarding such a separator heating unit, see Korean Patent Application Publication No. 10-2020-0023853.

(77) The separator heating unit may include a pair of bodies (not illustrated) and a separator heater (not illustrated) for heating the body. The pair of bodies may be located on opposing sides of the separator **4** while being spaced apart from each other by a predetermined distance so as to allow the separator **4** to pass through. The separator **4** may, for example, pass through, while not being in contact with, the separator heating unit such that the separator **4** may be heated in a non-contact manner. In some arrangements, each body of the pair of bodies of the separator heating unit may be formed in, for example, a rectangular block shape.

(78) As in the example of the electrode assembly manufacturing apparatus **100**, the first electrode supply unit **30** may be configured for supplying the first electrode **1** to the stack table **10** and for stacking the first electrode **1** on the stack table **10**. The first electrode supply unit **30** may include a first electrode seating table **31** on which the first electrode **1** is seated before being stacked on the stack table **10**. Further, the first electrode supply unit **30** may include a first electrode roll **33**, a first cutter **34**, a first conveyor **35**, and a first electrode supply head **36**. In the first electrode supply unit **30**, one of the first electrodes **1** may be supplied to the first electrode seating table **31** while a first electrode sheet from which the first electrodes **1** are formed wound around the first electrode roll **33** may be gradually unwound. The first cutter **34** may cut the first electrode **1** from the first electrode sheet supplied from the first electrode roll **33** to a preset length. The first cutter **34** may cut the first electrode sheet such that a first electrode tab **1a** protrudes from an end of the first electrode **1**.

(79) The first electrode **1** cut by the first cutter **34** may be supplied to the first conveyor **35**, and the first conveyor, which may be in the form of a belt as shown, may move the first electrode **1** to the first electrode seating table **31**. The first electrode supply head **36** may pick up (e.g., via a vacuum fitting, suction cups or similar fitting, or other temporary form of attachment such as a magnetic attachment) the first electrode **1** placed on the first conveyor **35** and position the first electrode **1** on the first electrode seating table **31**.

(80) As further shown, the first electrode supply unit **30** may include a first transfer head **32** and a first moving unit **37** from which the first transfer head may extend and may be oscillated. The first transfer head **32** may pick up (e.g., via a vacuum fitting, suction cups or similar fitting, or other temporary form of attachment such as a magnetic attachment) the first electrode **1** seated on the first electrode seating table **31**. In some arrangements, the first transfer head **32** may include a vacuum suction unit (not illustrated) on the bottom surface of the transfer head that may be configured for suctioning the first electrode **1** via a vacuum suction port to affix the first electrode **1**

to the bottom surface of the first transfer head **32**. A passage formed in the first transfer head **32** may connect the vacuum suction port and a vacuum suction device (not illustrated).

(81) The first moving unit **37** may be configured for picking up the first electrode **1** seated on the first electrode seating table **10** and for moving the first transfer head **32** to a position overlying the stack table **10** where the transfer head **32** may release, e.g., by reducing or removing vacuum suction or other force being applied to the first electrode **1** to hold the first electrode against the transfer head. In this manner, the first transfer head **32** may transfer the first electrode **1** from the first electrode seating table **31** onto a section of the separator **4** resting on or overlying the stack table **10** via other electrodes **1, 2**.

(82) The second electrode supply unit **40** may have or may essentially have a mirror configuration of the first electrode supply unit **30**. In this manner, the second electrode supply unit **40** may supply the second electrode **2** to a portion of the stack **S** resting, e.g., mounted, on the stack table **10** at that time and stack the second electrode **2** on such portion of the stack **S** on the stack table **10**.

(83) The second electrode supply unit **40** may include a second electrode seating table **41** on which the second electrode **2** is seated before being moved and stacked onto the portion of the stack **S** on the stack table **10**.

(84) The second electrode supply unit **40** may include a second electrode roll **43** around which a second electrode sheet from which the second electrode **2** is formed is wound, a second cutter **44** for cutting at regular intervals the second electrode sheet to form the second electrodes **2** in a predetermined size while unwinding the second electrode sheet from the second electrode roll **43**, a second conveyor **45** for moving the second electrode **2** cut by the second cutter **44**, and a second electrode supply head **46** for picking up the second electrode **2** moved by the second conveyor **45** and seating the second electrode **2** on the second electrode seating table **41**.

(85) Like the first cutter **34**, the second cutter **44** may cut the second electrode sheet such that the formed second electrodes **2** each include a second electrode tab **2a** protruding from an end of the second electrode **2**.

(86) Further, the second electrode supply unit **40** may include a second transfer head **42** for picking up the second electrode **2** seated on the second electrode seating table **41** and a second moving unit **47** configured for moving the second transfer head **42** to a position overlying the stack table **10** where the transfer head **42** may release, e.g., by reducing or removing vacuum suction or other force being applied to the second electrode **2** to hold the second electrode against the transfer head, so that the second transfer head **42** may stack the second electrode **2** onto a portion of the stack **S** on the stack table **10** at that time. The second transfer head **42** may be formed in the same manner as the first transfer head **32** such that the second electrode **2** may be temporarily affixed to the second transfer head **42** on a bottom surface of the second transfer head **42**.

(87) The side sealing device **60** may heat up at least one side surface of the stack **S** with the separator **4** surrounding the outermost portion of the stack. That is, the side sealing device **60** may apply heat to at least one side surface of the stack **S** to impart or increase adhesive force to a coating layer component applied to one surface of the separator **4** and facing towards the electrodes **1, 2**.

(88) The pressing direction of the side sealing device **60** may be perpendicular to the pressing direction of the press unit **50** described further herein.

(89) In some arrangements, the side sealing device **60** may include a pair of heating bars **60a** and **60b**. The pair of heating bars **60a** and **60b** may be moved towards and away from each other and compress the stack **S** in a direction from the side and towards the center of the stack. That is, the side sealing device **60** may heat and compress the stack **S** from the side of the stack **S**.

(90) The side surface of the stack **S** is a surface that includes the folded parts **P** of the stack **S**. Preferably, the side surface of the stack is not located on the same side of electrodes **1, 2** that electrode tabs **1a** are located.

(91) The stack **S** may include one or more sequentially stacked first electrodes **1**, sections of

separators **4**, and second electrodes **2** in which an outermost portion of the separator **4** surrounds the outermost portion of the stack. The side sealing device **60** may heat and compress the side surface of the stack **S** and thereby the folded parts **P** included in the stack **S** by heating and compressing the outermost portion of the separator **4** (hereinafter, the outermost separator) surrounding the outermost portion of the stack **S**. Therefore, the side sealing device **60** may bond the plurality of folded parts **P** included in the stack **S** by heating and compressing the side surface of the stack **S** and thereby bond an inner surface of the outermost separator **4** to the folded parts **P** of the separator **4**, the first electrode **1**, and the second electrode **2** facing the inner surface of the outermost separator **4**.

(92) The electrode assembly manufacturing apparatus **100** may further include the press unit **50**. The press unit **50** is heated for compressing of the stack **S**. Pressing of the press unit **50** may bond the first electrode **1**, the separator **4**, and the second electrode **2**.

(93) The press unit **50** may include a pair of pressing blocks **50a** and **50b** that may be located adjacent to top and bottom surfaces of the stack **S**. The pair of pressing blocks **50a** and **50b** may be moved in directions towards each other to compress the top and bottom surfaces of the **S** and then moved away from each other following such compression.

(94) When the separator **4** is configured to surround the outer surface of the stack **S**, the space between inner surface portions of the outermost separator **4** and side portions of the first and second electrodes **1**, **2** and the separator **4** facing the inner surface portions of the separator **4** may be bonded. In this configuration, the outermost separator **4** may include an upper surface, a lower surface, and two opposing side surfaces extending between the upper and the lower surfaces of the outermost separator **4** when surrounding the stack **S**.

(95) Accordingly, when the electrode assembly **10** is formed by stacking the first electrode **1**, the sections of the separator **4**, and the second electrode **2**, issue of the press unit **50** inhibits relative displacement of the first and second electrodes **1** and **2** and the separator **4** and thereby inhibits the stacking form from being undone.

(96) The press unit **50** may further include a press heater (not illustrated) for heating the pair of pressing blocks **50a** and **50b** such that the pair of pressing blocks **50a** and **50b** may heat up the stack **S** while compressing the stack. In this manner, when the stack **S** is compressed with the press unit **50**, thermal fusion and thereby stronger bonds between each first electrode **1** and sections of the separator **4** adjacent to the first electrode and between the second electrode **2** and sections of the separator **4** adjacent to the second electrode may be better achieved.

(97) As best shown in FIG. **4**, each of the pair of pressing blocks **50a** and **50b** may be formed with a flat pressing surface in which either one or both of the lengths and the widths of the pressing surfaces may be formed to be longer than the corresponding lengths and widths of the stack **S**.

(98) Further, the pair of pressing blocks **50a** and **50b** may be provided as a quadrangular block in the form of a rectangular parallelepiped.

(99) In some arrangements, the electrode assembly manufacturing apparatus **100** may further include a third moving unit (not illustrated) attached to and configured for rotating or otherwise moving a third transfer head (not illustrated). The third moving unit and the third transfer head may be the same as or similar to the first and second moving units **37**, **47** and the first and the second transfer heads **32**, **42**, respectively.

(100) In some arrangements, the third transfer head may suction the stack **S** seated on the stack table **10**. The third transfer head may include a vacuum suction unit on a bottom surface to suction the stack **S** via the vacuum suction port and thereby temporarily affix the stack **S** to the bottom surface of the third transfer head. A passage connecting the vacuum suction port and the vacuum suction generation device may be formed in the third transfer head.

(101) The third moving unit may be configured to move, e.g., via either one or both of translation and rotation, the third transfer head to the side sealing device **60** so that the stack **S** seated on the stack table **10** is movable to the side sealing device **60**.

(102) In some arrangements, the third transfer head may be temporarily affixed, in the manner described above, to the stack S when the stack is seated on the press unit **50**. In such arrangements, the third moving unit may be configured to move, e.g., via either one or both of translation and rotation, the third transfer head to the side sealing device **60** so that the stack S seated on the press unit **50** is movable to the side sealing device **60**.

(103) Referring now to FIG. **6**, an electrode assembly manufacturing process may include a stack manufacturing operation **S10** and a side sealing operation **S20**.

(104) In the stack manufacturing operation **S10**, a stack may be manufactured by supplying and stacking a first electrode, e.g., first electrode **1**, a separator, e.g., separator **4**, and a second electrode, e.g., second electrode **2**, to an in-process stack on a stack table, e.g., stack table **10**.

(105) In a step **S11** of the stack manufacturing operation **S10**, a section of the separator is supplied to the stack table. In some arrangements, this section of the separator is mounted to the stack table by a holding mechanism such as but not limited to a clamp or set of clamps or other clamping mechanism. In a step **S12**, the stack table is rotated in a direction towards a first electrode supply unit, e.g., first electrode supply unit **30**. In a step **S13**, the first electrode is supplied and then stacked onto the separator section mounted or otherwise resting on the stack table. In a step **S14**, the stack table is rotated in a direction of a second electrode supply unit, e.g., second electrode supply unit **40**, such that a further section of the separator folds onto and overlies the first electrode. In a step **S15**, the second electrode is supplied and then stacked onto a further section of the separator. In a step **S16**, the operations **S12**, **S13**, **S14**, and **S15** are repeated to sequentially add one or more further first electrodes, sections of the separator, and one or more further second electrodes. In repeating the operation **S12**, a still further section of the separator folds onto and overlies the second electrode via rotation of the stack table before the next first electrode is supplied and then stacked onto that still further section of the separator. Via the alternating rotation of the stack table, the separator may be stacked in a zigzag manner between first and second electrodes.

(106) In addition, in a step **S17** of the stack manufacturing operation **S10**, the outermost portion of the stack may be surrounded by the separator by rotating the separator in one direction. Here, the outermost portion of the stack includes an upper surface, a lower surface, and both opposite side surfaces of the stack. Each of the side surfaces may extend in planes parallel to the stacking direction of the stack. Each of the side surfaces may exclude all surfaces on which an electrode tab, e.g., electrode tab **1a** is located. The upper and lower surfaces of the stack each include a surface perpendicular to one or both of the side surfaces of the stack.

(107) In the side sealing operation **S20**, at least one side surface of the stack may be heated. In this operation, one or both of the opposite side surfaces of the stack are heated and compressed to compress the stack. In this step, a pair of heating bars, e.g., heating bars **60a** and **60b**, may be pressed against the separator along the side surfaces of the stack for a time of 10 seconds or less while the heating bars are at a side sealing temperature of 100° C. to 200° C.

(108) When the side sealing temperature is less than 100° C., sufficient adhesive forces may not be exhibited by a binder applied to the separator, and when the side sealing temperature exceeds 200° C., or when the pressing time exceeds 10 seconds, the increase in the adhesive effect may be insignificant compared to the energy supplied to heat the pair of heating bars.

(109) In addition, during the side sealing operation **S20**, at least one side surface of the stack may be compressed at a pressure in a range from 0.1 MPa to 1.5 MPa. Preferably, the one or more side surfaces may be pressed at a pressure in a range from 0.1 MPa to 1 MPa and more preferably at a pressure in a range from 0.1 MPa to 0.5 MPa.

(110) That is, in the side sealing operation **S20**, both side surfaces of the stack may be compressed in directions perpendicular to the side surfaces and towards the center plane of the stack while heating both side surfaces of the stack at the same time.

(111) When the pressure compressing the side surfaces of the covered stack satisfies the above-noted pressure range, damage to the first electrode and the second electrode may be prevented or at

least inhibited by the contact and bonding of the outermost separator and the folded parts.

(112) In a step **S30**, the electrode assembly manufacturing process may further include heating and compressing the stack. In this step, a pair of heated pressing blocks, e.g., the pair of pressing blocks **50a** and **50b** may compress the stack in a downward direction and optionally an upward direction towards the stack generally parallel to the side surfaces of the stack. Due to the heat conducted from the pair of pressing blocks, adhesive forces between the binder and the separator to which the binder is applied may be improved, and the separator and the first and second electrodes further may be bonded to each other by pressure.

(113) With reference to FIG. 7, each side section **4b** may be bent one or more times in directions parallel to the stacking direction of the stack **S**. In this manner, in the electrode assembly **10** with the second separator **5** wound around the stack **S**, the distance between an end of the first electrode **1** and a portion of the inner separator surface of the second separator **5** facing the end of the first electrode **1** and the distance between an end of the second electrode **2** and a portion of the inner separator surface of the second separator **5** facing the end of the second electrode **2** are reduced such that the overall width of the electrode assembly **10** may be reduced.

(114) The distance between the first electrode **1** or the second electrode **2** and a portion of the inner separator surface of the second separator **5** adjacent ends of the first electrode **1** or the second electrode **2** of the electrode assembly **10** may be reduced by 50% to 95% with a 100% reduction of the entire length of the side section **4b**. The entire length of the side section **4b** is the distance from the end of the first electrode **1** or the second electrode **2** to the end of the side section **4b** that is in contact with the second separator **5** when the side section **4b** is in an unbent state.

(115) As the length of the side section **4b** is reduced by 50% to 95% compared to the entire length of that side section **4b**, a portion of that side section **4b** in which the first electrode **1** and the second electrode **2** are not included is reduced, and thus the electrode density and the energy density of the electrode assembly **10** may be increased.

(116) Wet adhesive force of the side section **4b** of the electrode assembly **10** and the second separator **5** that is bonded to the side section **4b** may be in a range from 40 gf/25 mm to 70 gf/25 mm.

Experimental Example

(117) The following experiment was performed to measure the adhesion rate between the end of the side section and the inner separator surface of the outermost portion of the separator acting as the second separator of the stack included in the electrode assembly and the battery properties according to the adhesion area.

Example Process

(118) The separator was folded in a zigzag shape, and a positive electrode and a negative electrode were alternately disposed between sections of the folded separator, and the outermost portion of the stack was surrounded with the separator for the manufacture of an electrode assembly. The electrode assembly according was manufactured by compressing the upper and lower surfaces of the stack by using the heated press unit to bond the entire stack and side sealing was performed by compressing both opposite side surfaces of the stack with the heated side sealing device.

Example 1

(119) Example 1 includes an electrode assembly in which a side section of a separator is bonded to an area of 30% of the total area of an inner separator surface of a separator positioned on the side of a stack facing the side section by compressing the stack with a pressure of 0.15 MPa by using a side sealing device.

Example 2

(120) Example 2 includes an electrode assembly in which a side section of a separator is bonded to an area of 80% of the total area of an inner separator surface of a separator positioned on the side of a stack facing the side section by compressing the stack with a pressure of 0.25 MPa by using a side sealing device.

Comparative Example 1

(121) Comparative Example 1 includes an electrode assembly in which a stack was compressed to a pressure of 0.05 MPa by using a side sealing device.

Comparative Example 2

(122) Comparative Example 2 includes an electrode assembly in which a side section of a separator is bonded to an area of 20% of the total area of an inner separator surface of a separator positioned on the side of a stack facing the side section by compressing the stack with a pressure of 0.10 MPa by using a side sealing device.

Comparative Example 3

(123) Comparative Example 3 includes an electrode assembly in which a side section of a separator is bonded to an area of 90% of the total area of an inner separator surface of a separator positioned on the side of a stack facing the side section by compressing the stack with a pressure of 0.30 MPa by using a side sealing device.

(124) TABLE-US-00001 TABLE 1 Press unit Side sealing Temperature Pressure Time Temperature Pressure Time (° C.) (Mpa) (s) (° C.) (Mpa) (s) Example 1 70 1.91 15 150 0.15 3 Example 2 70 1.91 15 150 0.25 3 Comparative 70 1.91 15 150 0.05 3 Example 1 Comparative 70 1.91 15 150 0.10 3 Example 2 Comparative 70 1.91 15 150 0.30 3 Example 3

(125) TABLE-US-00002 TABLE 2 Negative Degree Lifting electrode of side of side damage sealing separator Example 1 None Good No Example 2 None Good No Comparative Measurement impossible Example 1 Comparative None Poor No Example 2 Comparative None Good Yes Example 3

(126) Table 2 shows the results of measurements of the damage to the negative electrode of the electrode assembly, the degree of adhesion between the side section and the portion of the separator located on the side of the side section, and the degree of lifting of the outermost portion of the separator positioned on the side of the electrode assembly.

(127) In this case, the degree of side sealing was observed visually by the degree of adhesion between the side section of the separator and the outermost portion of the separator acting as the second separator. The lifting of the second or side separator means that the second separator is pushed to the upper surface or the lower surface of the electrode assembly, and a part of the separator positioned on the upper surface and the lower surface of the electrode assembly does not adhere to the electrode.

(128) Referring to Table 2, in Comparative Example 1, since the pressure applied by the side sealing device was low, the electrode assembly could not be compressed such that it was not possible to measure the damage to the negative electrode, the degree of side sealing, or the degree of lifting of the second separator.

(129) In Comparative Example 2, it can be seen that although the side sealing device compresses the side surface of the electrode assembly, the second separator positioned on the side of the electrode assembly did not move to the side section due to low pressure such that the adhesion between the side section and the second separator was poor.

(130) In Comparative Example 3, it can be seen that the pressure applied by the side sealing device to the side of the electrode assembly was large. As such, the second separator located on the side of the electrode assembly climbed up the anode and the anode pushed the separator positioned on the upper or lower surface of the electrode assembly. It can be confirmed visually that the separator positioned on the upper or lower surface of the electrode assembly is folded.

(131) In the forgoing, the present invention has been described with reference to exemplary embodiments, but those skilled in the art may appreciate that the present invention may be variously modified without departing from the spirit and the scope of the present invention as set forth in the appended claims.

Claims

1. An electrode assembly manufacturing apparatus for preparing a stack comprising a first electrode, a second electrode, and a section of a first separator between the first and the second electrodes, the apparatus comprising: a press unit configured for compressing opposing upper and lower surfaces of the stack; and a side sealing device configured for heating at least one side surface of the stack extending between the upper and the lower surfaces of the stack to bond either a portion of the first separator separate from the section of the separator and covering a portion of the side surface of the stack or a portion of a second separator covering the side surface of the stack to the side surface of the stack.
2. The electrode assembly manufacturing apparatus of claim 1, wherein the side sealing device is further configured for compressing the side surface of the stack and the one of the portion of the first separator or the portion of the second separator.
3. The electrode assembly manufacturing apparatus of claim 2, wherein the bond of the side surface of the stack to the one of the portion of the first separator or the portion of the second separator to the side surface of the stack has an adhesive force in a range from 40 gf/25 mm to 70 gf/25 mm.
4. The electrode assembly manufacturing apparatus of claim 1, wherein the side sealing device includes a pair of heating bars, and the pair of heating bars are moveable in directions towards each other to compress the side surface of the stack.
5. The electrode assembly manufacturing apparatus of claim 1, wherein the pair of heating bars are configured for being heated to a temperature of 100° C. to 200° C.
6. The electrode assembly manufacturing apparatus of claim 1, wherein the pair of heating bars are configured to be pressed against the one of the portion of the first separator or the portion of the second separator for a time of 10 seconds or less while the heating bars are at a temperature of 100° C. to 200° C.
7. The electrode assembly manufacturing apparatus of claim 1, wherein the press unit is further configured for heating the stack while compressing the stack.
8. The electrode assembly manufacturing apparatus of claim 1, wherein the press unit is further configured for compressing the upper surface of the stack in a direction along which the stack is stacked.
9. The electrode assembly manufacturing apparatus of claim 1, wherein the press unit includes a pair of pressing blocks, and wherein the pair of the pressing blocks are configured for movement towards each other to compress the upper and the lower surfaces of the stack.
10. The electrode assembly manufacturing apparatus of claim 9, wherein each of the pair of the pressing blocks includes a pressing surface, and wherein the pressing surfaces are configured for contacting respective ones of the upper and the lower surfaces of the stack to compress the upper and the lower surfaces such that the upper and the lower surfaces each define a plane.
11. The electrode assembly manufacturing apparatus of claim 9, wherein the press unit includes a press heater configured for heating the pair of the pressing blocks.
12. The electrode assembly manufacturing apparatus of claim 9, wherein each of the pair of the pressing blocks of the press unit includes a pressing surface that defines a plane, and wherein the pressing surfaces of the pressing blocks have either one of or both a width that is longer than a width of the stack and a length that is longer than a length of the stack.
13. The electrode assembly manufacturing apparatus of claim 1, wherein the stack is movable to the side sealing device while supported by the press unit.
14. The electrode assembly manufacturing apparatus of claim 1, further comprising a stack table configured for supporting the stack, wherein the stack is movable to the side sealing device while supported by the stack table.
15. The electrode assembly manufacturing apparatus of claim 1, further comprising the stack.

16. The electrode assembly manufacturing apparatus of claim 15, further comprising the one of the portion of the first separator or the portion of the second separator covering the side surface of the stack, wherein the one of the portion of the first separator or the portion of the second separator is wound around the stack, and wherein the press unit is configured for heating and compressing the one of the portion of the first separator or the portion of the second separator.
17. The electrode assembly manufacturing apparatus of claim 15, further comprising the one of the portion of the first separator or the portion of the second separator, wherein the one of the portion of the first separator or the portion of the second separator is wound around the stack, and wherein the side sealing device is configured for heating and compressing the one of the portion of the first separator or the portion of the second separator.
18. The electrode assembly manufacturing apparatus of claim 1, wherein the stack comprises a plurality of first electrodes including the first electrode and a plurality of second electrodes including the second electrode, and the first separator comprises a plurality of sections including the section of the first separator, each section of the first separator extending between adjacent ones of the first and second electrodes, wherein the first separator comprises a plurality of portions separate from the sections of the first separator including the portion of the first separator, each portion of the first separator covering a respective portion of the side surface of the stack, and wherein the side sealing device is configured for heating at least one side surface of the stack extending between the upper and the lower surfaces of the stack to bond either two or more of the portions of the first separator or the portion of the second separator to the side surface of the stack.
19. The electrode assembly manufacturing apparatus of claim 1, wherein the two or more of the portions of the first separator is all of the portions of the first separator separate from the sections of the first separator and covering the respective portions of the side surface of the stack.
20. An electrode assembly manufacturing apparatus for preparing a stack comprising a first electrode, a second electrode, and a first section of a first separator between the first and the second electrodes, the apparatus comprising: the stack; either a portion of the first separator separate from the first section of the separator and covering a portion of the side surface of the stack or a portion of a second separator covering the side surface of the stack; and a side sealing device configured for heating at least one side surface of the stack to bond the one of the portion of the first separator or the portion of the second separator to the side surface of the stack.
21. The electrode assembly manufacturing apparatus of claim 20, wherein the side sealing device is further configured for compressing the side surface of the stack and the one of the portion of the first separator or the portion of the second separator.
22. The electrode assembly manufacturing apparatus of claim 21, wherein the bond of the side surface of the stack to the one of the portion of the first separator or the portion of the second separator to the side surface of the stack has an adhesive force in a range from 40 gf/25 mm to 70 gf/25 mm.
23. The electrode assembly manufacturing method of claim 20, wherein the stack further comprises a second section of the first separator, the second section forming a portion of the side surface of the stack.
24. An electrode assembly manufacturing method for manufacturing a stack, the stack comprising first and second electrodes with a section or sections of a first separator disposed between the first and the second electrodes, the method comprising: heating at least one side surface of the stack extending between opposing upper and lower surfaces of the stack to bond either a portion of the first separator separate from the section or sections of the separator disposed between the first and the second electrodes and covering the side surface of the stack or a portion of a second separator covering the side surface of the stack to the side surface of the stack.
25. The electrode assembly manufacturing method of claim 24, further comprising: compressing the upper and the lower surfaces of the stack.
26. The electrode assembly manufacturing method of claim 24, wherein the heating step results in a

bond of the portion of the first separator or the portion of the second separator to the side surface of the stack with an adhesive force in a range from 40 gf/25 mm to 70 gf/25 mm.

27. An electrode assembly fabricated by the electrode assembly manufacturing method of claim 24.

28. The electrode assembly manufacturing apparatus of claim 1, wherein the side surface of the stack comprises adjacent bonded side sections of the first separator that extend beyond peripheral edges of the first and second electrodes.

29. The electrode assembly manufacturing apparatus of claim 20, wherein the side surface of the stack comprises adjacent bonded side sections of the first separator that extend beyond peripheral edges of the first and second electrodes.

30. The electrode assembly manufacturing method of claim 24, wherein the side surface of the stack comprises adjacent bonded side sections of the first separator that extend beyond peripheral edges of the first and second electrodes.
