

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12410090
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Gross; Timothy Michael et al.

Non-iox glasses with high coefficient of thermal expansion and preferential fracture behavior for thermal tempering

Abstract

The disclosure relates to glass compositions with high coefficients of thermal expansion and low fracture toughness designed for thermal tempering. These glasses are ideally suited to produce a “dicing” pattern when thermally tempered, even when thin (<3 mm). Disclosed glasses have high thermal expansions at low and high temperatures to produce increased temper stresses once quenched, coupled with low fracture toughness which promotes crack bifurcation and enhanced frangibility. Methods of making such glasses are also provided.

Inventors: Gross; Timothy Michael (Painted Post, NY), Lezzi; Peter Joseph (Corning, NY)

Applicant: CORNING INCORPORATED (Corning, NY)

Family ID: 64665627

Assignee: CORNING INCORPORATED (Corning, NY)

Appl. No.: 18/203890

Filed: May 31, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230312395 A1	Oct. 05, 2023

Related U.S. Application Data

continuation parent-doc US 16767191 US 11708296 WO PCT/US2018/063404 20181130 child-doc US 18203890
us-provisional-application US 62592683 20171130

Publication Classification

Int. Cl.: C03C3/097 (20060101); C03B27/012 (20060101); C03C3/091 (20060101)

U.S. Cl.:

CPC C03C3/097 (20130101); C03B27/012 (20130101); C03C3/091 (20130101);

Field of Classification Search

CPC: C03C (3/097); C03C (3/091)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
1951950	12/1933	Rising	N/A	N/A
2106527	12/1937	Hostetter	N/A	N/A
2145119	12/1938	Littleton	N/A	N/A
2177336	12/1938	Shaver et al.	N/A	N/A
3107196	12/1962	Acloque	N/A	N/A
3169900	12/1964	Ermlich	N/A	N/A
3174839	12/1964	Long	N/A	N/A
3223499	12/1964	Cypher et al.	N/A	N/A
3223501	12/1964	Fredley et al.	N/A	N/A
3223549	12/1964	Fredley et al.	N/A	N/A
3225349	12/1964	Thor	N/A	N/A
3279906	12/1965	Baker	N/A	N/A
3287200	12/1965	Hess et al.	N/A	N/A
3293015	12/1965	Fredley et al.	N/A	N/A
3332759	12/1966	McMaster et al.	N/A	N/A
3374078	12/1967	Wright	N/A	N/A
3409422	12/1967	Gulotta	N/A	N/A
3423198	12/1968	McMaster et al.	N/A	N/A
3445316	12/1968	Megles	N/A	N/A
3449102	12/1968	Nedelec et al.	N/A	N/A
3497340	12/1969	Dennison et al.	N/A	N/A
3556757	12/1970	Kozlowski et al.	N/A	N/A
3558415	12/1970	Rieser et al.	N/A	N/A
3607169	12/1970	Coxe	N/A	N/A
3637453	12/1971	Simmons	N/A	N/A
3673049	12/1971	Giffen et al.	N/A	N/A
3679388	12/1971	Giddings et al.	N/A	N/A
3744921	12/1972	Weller et al.	N/A	N/A
3753674	12/1972	Ohlberg et al.	N/A	N/A
3776712	12/1972	Wilde	N/A	N/A
3793127	12/1973	Wartenberg	N/A	N/A
3794476	12/1973	Michalik et al.	N/A	N/A
3830540	12/1973	Sperry	N/A	N/A

3844758	12/1973	Wartenberg	N/A	N/A
3850679	12/1973	Sopko et al.	N/A	N/A
3883339	12/1974	Michalik et al.	N/A	N/A
3890128	12/1974	Melling et al.	N/A	N/A
3902884	12/1974	Harrison	N/A	N/A
3929442	12/1974	Neely, Jr.	N/A	N/A
3931438	12/1975	Beall et al.	N/A	N/A
3936291	12/1975	McMaster	N/A	N/A
3973943	12/1975	Seymour	N/A	N/A
3994711	12/1975	McMaster	N/A	N/A
4081254	12/1977	Matsumoto et al.	N/A	N/A
4091163	12/1977	Clausen	N/A	N/A
4107460	12/1977	Grunza et al.	N/A	N/A
4128690	12/1977	Boardman et al.	N/A	N/A
4194898	12/1979	Marsh et al.	N/A	N/A
4198226	12/1979	Marsh et al.	N/A	N/A
4198463	12/1979	Greenhalgh	N/A	N/A
4204845	12/1979	Shields et al.	N/A	N/A
4214886	12/1979	Shay et al.	N/A	N/A
4286052	12/1980	Ernsberger	N/A	N/A
4300936	12/1980	Quillevere et al.	N/A	N/A
4314836	12/1981	Seymour	N/A	N/A
4319907	12/1981	Pike	N/A	N/A
4332605	12/1981	Wright et al.	N/A	N/A
4372774	12/1982	Cross et al.	N/A	N/A
4400193	12/1982	Cross et al.	N/A	N/A
4470838	12/1983	Mcmaster et al.	N/A	N/A
4471024	12/1983	Pargamin et al.	N/A	N/A
4494972	12/1984	Marsh et al.	N/A	N/A
4516999	12/1984	Kiefer et al.	N/A	N/A
4662926	12/1986	Aratani et al.	N/A	N/A
4690871	12/1986	Gordon	N/A	N/A
4744676	12/1987	Lind	N/A	N/A
4773926	12/1987	Letemps et al.	N/A	N/A
4826525	12/1988	Chesworth et al.	N/A	N/A
4913720	12/1989	Gardon et al.	N/A	N/A
4973163	12/1989	Sakai et al.	N/A	N/A
4985275	12/1990	Takemura et al.	N/A	N/A
5009694	12/1990	Nishitani et al.	N/A	N/A
5057375	12/1990	Gordon	N/A	N/A
5071796	12/1990	Jones et al.	N/A	N/A
5121329	12/1991	Crump	N/A	N/A
5213440	12/1992	Yeh et al.	N/A	N/A
5236488	12/1992	Vehmas	N/A	N/A
5285517	12/1993	Wu	N/A	N/A
5340433	12/1993	Crump	N/A	N/A
5500287	12/1995	Henderson	N/A	N/A
5626911	12/1996	Bertin et al.	N/A	N/A
5643649	12/1996	Hagan et al.	N/A	N/A
5654057	12/1996	Kitayama et al.	N/A	N/A

5676722	12/1996	Seidel et al.	N/A	N/A
5735923	12/1997	Hisaeda	N/A	N/A
5795659	12/1997	Meelu et al.	N/A	N/A
5885316	12/1998	Sato et al.	N/A	N/A
5931981	12/1998	McMaster et al.	N/A	N/A
5938808	12/1998	McMaster et al.	N/A	N/A
5938810	12/1998	De Vries et al.	N/A	N/A
5939175	12/1998	Sugiura	N/A	N/A
5972513	12/1998	Yoshizawa	N/A	N/A
6053011	12/1999	Lisec	N/A	N/A
6079227	12/1999	Yoshizawa et al.	N/A	N/A
6094943	12/1999	Okuda et al.	N/A	N/A
6117283	12/1999	Chen et al.	N/A	N/A
6183565	12/2000	Granneman et al.	N/A	N/A
6200665	12/2000	Seto	N/A	N/A
6295842	12/2000	McMaster	N/A	N/A
6336775	12/2001	Morita et al.	N/A	N/A
6353283	12/2001	Ghosh et al.	N/A	N/A
6370917	12/2001	Kato et al.	N/A	N/A
6412309	12/2001	Kajii et al.	N/A	N/A
6442017	12/2001	Ewing et al.	N/A	N/A
6461439	12/2001	Granneman et al.	N/A	N/A
6472800	12/2001	Goda et al.	N/A	N/A
6598427	12/2002	Douche et al.	N/A	N/A
6613685	12/2002	Granneman et al.	N/A	N/A
6642017	12/2002	Weiser	N/A	N/A
6656597	12/2002	Takahara	N/A	N/A
6713180	12/2003	Torr et al.	N/A	N/A
6722160	12/2003	Nemugaki et al.	N/A	N/A
6770851	12/2003	Granneman et al.	N/A	N/A
6805749	12/2003	Granneman et al.	N/A	N/A
6826929	12/2003	Boaz	N/A	N/A
6877250	12/2004	Granneman et al.	N/A	N/A
6881485	12/2004	Kato et al.	N/A	N/A
6881931	12/2004	Vehmas et al.	N/A	N/A
6977710	12/2004	Akiyama et al.	N/A	N/A
7022627	12/2005	Granneman et al.	N/A	N/A
7048488	12/2005	Kuznetsov et al.	N/A	N/A
7153798	12/2005	Bordeaux et al.	N/A	N/A
7215262	12/2006	Suzuki et al.	N/A	N/A
7261939	12/2006	Hallett et al.	N/A	N/A
7306848	12/2006	Tominaga et al.	N/A	N/A
7312156	12/2006	Granneman et al.	N/A	N/A
7341968	12/2007	Yoda et al.	N/A	N/A
7367205	12/2007	Boaz	N/A	N/A
7410355	12/2007	Granneman et al.	N/A	N/A
7566673	12/2008	Kawai	N/A	N/A
7666511	12/2009	Ellison et al.	N/A	N/A
7694532	12/2009	Boaz	N/A	N/A
7867932	12/2010	Beall	N/A	N/A

7908885	12/2010	Devitt	N/A	N/A
8074473	12/2010	Nitschke et al.	N/A	N/A
8233433	12/2011	Kalhan	N/A	N/A
8234883	12/2011	Krall et al.	N/A	N/A
8289342	12/2011	Matsumoto	N/A	N/A
8415013	12/2012	Barefoot et al.	N/A	N/A
8524804	12/2012	Kitano et al.	N/A	N/A
8585463	12/2012	Nakae	N/A	N/A
8679599	12/2013	Grzybowski et al.	N/A	N/A
8713967	12/2013	Danielson et al.	N/A	N/A
8713972	12/2013	Lakota et al.	N/A	N/A
8728961	12/2013	Lautenschlaeger et al.	N/A	N/A
8759238	12/2013	Chapman et al.	N/A	N/A
8765262	12/2013	Gross	N/A	N/A
8769990	12/2013	Saito et al.	N/A	N/A
8776548	12/2013	Dannoux et al.	N/A	N/A
8802581	12/2013	Dejneka et al.	N/A	N/A
8821999	12/2013	Grzybowski et al.	N/A	N/A
8854623	12/2013	Fontaine et al.	N/A	N/A
8916013	12/2013	Hong et al.	N/A	N/A
8946103	12/2014	Dejneka et al.	N/A	N/A
8951927	12/2014	Dejneka et al.	N/A	N/A
8997521	12/2014	Vehmas et al.	N/A	N/A
9003835	12/2014	Lock	N/A	N/A
9039886	12/2014	Gong et al.	N/A	N/A
9073291	12/2014	Bookbinder et al.	N/A	N/A
9137892	12/2014	Bando et al.	N/A	N/A
9145329	12/2014	Drake et al.	N/A	N/A
9156724	12/2014	Gross	N/A	N/A
9296638	12/2015	Lezzi et al.	N/A	N/A
9478449	12/2015	Vermont et al.	N/A	N/A
9522836	12/2015	Gulati et al.	N/A	N/A
9552836	12/2016	Ramakrishnan et al.	N/A	N/A
9586861	12/2016	Borrelli et al.	N/A	N/A
9725359	12/2016	Weber	N/A	N/A
9761828	12/2016	Dabich et al.	N/A	N/A
9776905	12/2016	Maschmeyer et al.	N/A	N/A
9783448	12/2016	Maschmeyer et al.	N/A	N/A
9802853	12/2016	Maschmeyer et al.	N/A	N/A
9957190	12/2017	Finkeldey et al.	N/A	N/A
9975801	12/2017	Maschmeyer et al.	N/A	N/A
10005691	12/2017	Maschmeyer et al.	N/A	N/A
10077204	12/2017	Maschmeyer et al.	N/A	N/A
10150699	12/2017	Baum et al.	N/A	N/A
10173923	12/2018	Kawamoto et al.	N/A	N/A
10195778	12/2018	Wolf et al.	N/A	N/A
10253550	12/2018	Kim et al.	N/A	N/A
11097974	12/2020	Lezzi et al.	N/A	N/A
2001/0007723	12/2000	Tokumoto	N/A	N/A

2002/0011481	12/2001	Melson et al.	N/A	N/A
2002/0145213	12/2001	Liu et al.	N/A	N/A
2003/0037569	12/2002	Arbab et al.	N/A	N/A
2003/0177790	12/2002	Langsdorf et al.	N/A	N/A
2004/0107733	12/2003	Yashizawa	N/A	N/A
2005/0099618	12/2004	Difoggio et al.	N/A	N/A
2005/0138892	12/2004	Misonou	N/A	N/A
2005/0266247	12/2004	Yoshizawa	N/A	N/A
2006/0054774	12/2005	Yassour et al.	N/A	N/A
2006/0121281	12/2005	Tamai et al.	N/A	N/A
2006/0179722	12/2005	Spindler	N/A	N/A
2006/0191292	12/2005	Carlomagno	N/A	N/A
2006/0219605	12/2005	Devitt	N/A	N/A
2006/0238100	12/2005	Miyata et al.	N/A	N/A
2007/0122580	12/2006	Krall et al.	N/A	N/A
2007/0271957	12/2006	Nakamura et al.	N/A	N/A
2008/0314403	12/2007	Rebours	N/A	N/A
2009/0069163	12/2008	Beall	N/A	N/A
2009/0092472	12/2008	Luo et al.	N/A	N/A
2009/0220761	12/2008	Dejneka et al.	N/A	N/A
2010/0035038	12/2009	Barefoot et al.	N/A	N/A
2010/0084016	12/2009	Aitken et al.	N/A	N/A
2010/0130251	12/2009	Chu	N/A	N/A
2010/0162761	12/2009	Carney et al.	N/A	N/A
2010/0183767	12/2009	Noordam et al.	N/A	N/A
2010/0279067	12/2009	Sabia et al.	N/A	N/A
2010/0279068	12/2009	Cook et al.	N/A	N/A
2010/0300535	12/2009	Aitken	136/260	C03C 3/091
2010/0300536	12/2009	Aitken et al.	N/A	N/A
2011/0014475	12/2010	Murata	N/A	N/A
2011/0045961	12/2010	Dejneka et al.	N/A	N/A
2011/0123832	12/2010	Matsumoto et al.	N/A	N/A
2011/0123833	12/2010	Endo et al.	N/A	N/A
2011/0165380	12/2010	Gahagan	428/156	C03C 3/091
2011/0200804	12/2010	Tomamoto et al.	N/A	N/A
2011/0281093	12/2010	Gulati et al.	N/A	N/A
2011/0289971	12/2010	Brown et al.	N/A	N/A
2011/0289972	12/2010	Brown et al.	N/A	N/A
2012/0052271	12/2011	Gomez et al.	N/A	N/A
2012/0144867	12/2011	Busch	N/A	N/A
2012/0145991	12/2011	Nam et al.	N/A	N/A
2012/0164314	12/2011	Labranche et al.	N/A	N/A
2012/0194974	12/2011	Weber et al.	N/A	N/A
2012/0247063	12/2011	Grzybowski et al.	N/A	N/A
2012/0258250	12/2011	Rodgers	N/A	N/A
2012/0281279	12/2011	Goto et al.	N/A	N/A
2012/0291707	12/2011	Granneman	N/A	N/A
2012/0328843	12/2011	Cleary et al.	N/A	N/A

2013/0008500	12/2012	Lin et al.	N/A	N/A
2013/0019639	12/2012	Saito et al.	N/A	N/A
2013/0047673	12/2012	Lee et al.	N/A	N/A
2013/0052347	12/2012	Kuznetsov et al.	N/A	N/A
2013/0059120	12/2012	Shi et al.	N/A	N/A
2013/0065795	12/2012	Allbritton et al.	N/A	N/A
2013/0071666	12/2012	Komori et al.	N/A	N/A
2013/0122284	12/2012	Gross	N/A	N/A
2013/0122313	12/2012	Gross	N/A	N/A
2013/0199448	12/2012	Granneman et al.	N/A	N/A
2013/0255314	12/2012	Allan et al.	N/A	N/A
2013/0291598	12/2012	Saito et al.	N/A	N/A
2013/0323444	12/2012	Ehemann et al.	N/A	N/A
2014/0010992	12/2013	Rendon Granados	N/A	N/A
2014/0026622	12/2013	Wang	N/A	N/A
2014/0050912	12/2013	Isono et al.	N/A	N/A
2014/0053605	12/2013	Mader	N/A	N/A
2014/0065401	12/2013	Donovan et al.	N/A	N/A
2014/0106172	12/2013	Dejneka et al.	N/A	N/A
2014/0113854	12/2013	Ni et al.	N/A	N/A
2014/0120279	12/2013	Demartino et al.	N/A	N/A
2014/0141217	12/2013	Gulati et al.	N/A	N/A
2014/0162000	12/2013	Son et al.	N/A	N/A
2014/0178663	12/2013	Varshneya et al.	N/A	N/A
2014/0218867	12/2013	Kim et al.	N/A	N/A
2014/0230492	12/2013	Murata	N/A	N/A
2014/0242391	12/2013	Ono et al.	N/A	N/A
2014/0290310	12/2013	Green	N/A	N/A
2014/0331716	12/2013	Ahmed et al.	N/A	N/A
2014/0352355	12/2013	Boudreau et al.	N/A	N/A
2014/0356605	12/2013	Adib et al.	N/A	N/A
2014/0370302	12/2013	Amin et al.	N/A	N/A
2014/0370303	12/2013	Jin et al.	N/A	N/A
2015/0027169	12/2014	Fredholm	N/A	N/A
2015/0030827	12/2014	Gomez	501/67	C03C 21/002
2015/0030834	12/2014	Morey et al.	N/A	N/A
2015/0031752	12/2014	Keil et al.	N/A	N/A
2015/0037552	12/2014	Mauro	N/A	N/A
2015/0051061	12/2014	Kiczenski et al.	N/A	N/A
2015/0052949	12/2014	Bayne et al.	N/A	N/A
2015/0082834	12/2014	Vehmas et al.	N/A	N/A
2015/0083200	12/2014	Hickman et al.	N/A	N/A
2015/0096331	12/2014	Rantala et al.	N/A	N/A
2015/0158276	12/2014	Thompson et al.	N/A	N/A
2015/0158757	12/2014	Amma et al.	N/A	N/A
2015/0166390	12/2014	Cha et al.	N/A	N/A
2015/0166401	12/2014	Yamamoto	N/A	N/A
2015/0175469	12/2014	Tabé	N/A	N/A
2015/0202845	12/2014	Cherekdjian et al.	N/A	N/A

2015/0218045	12/2014	Balcom et al.	N/A	N/A
2015/0240038	12/2014	Macedo et al.	N/A	N/A
2015/0246846	12/2014	Choju et al.	N/A	N/A
2015/0251353	12/2014	Rodgers et al.	N/A	N/A
2015/0251377	12/2014	Cleary et al.	N/A	N/A
2015/0266235	12/2014	Page	N/A	N/A
2015/0274015	12/2014	Wachinger et al.	N/A	N/A
2015/0307385	12/2014	Klein et al.	N/A	N/A
2015/0314571	12/2014	Cites et al.	N/A	N/A
2015/0329406	12/2014	Kawamoto et al.	N/A	N/A
2015/0343704	12/2014	Stahl et al.	N/A	N/A
2015/0368153	12/2014	Pesansky et al.	N/A	N/A
2016/0002103	12/2015	Wang et al.	N/A	N/A
2016/0031739	12/2015	Lezzi et al.	N/A	N/A
2016/0031741	12/2015	Maschmeyer et al.	N/A	N/A
2016/0031742	12/2015	Maschmeyer et al.	N/A	N/A
2016/0031743	12/2015	Maschmeyer et al.	N/A	N/A
2016/0031744	12/2015	Maschmeyer et al.	N/A	N/A
2016/0031752	12/2015	Maschmeyer et al.	N/A	N/A
2016/0031753	12/2015	Maschmeyer et al.	N/A	N/A
2016/0082705	12/2015	Fisher et al.	N/A	N/A
2016/0168023	12/2015	Baum et al.	N/A	N/A
2016/0194233	12/2015	Van Pelt	N/A	N/A
2016/0194239	12/2015	Seto	N/A	N/A
2016/0207819	12/2015	Cleary et al.	N/A	N/A
2016/0250825	12/2015	Cleary et al.	N/A	N/A
2016/0250982	12/2015	Fisher et al.	N/A	N/A
2016/0281233	12/2015	Granneman et al.	N/A	N/A
2016/0304352	12/2015	Ozyilmaz et al.	N/A	N/A
2016/0326051	12/2015	Kim	N/A	N/A
2017/0008377	12/2016	Fisher et al.	N/A	N/A
2017/0022100	12/2016	Masters et al.	N/A	N/A
2017/0072613	12/2016	Bracha et al.	N/A	N/A
2017/0113440	12/2016	Rickerl et al.	N/A	N/A
2017/0158543	12/2016	Metz et al.	N/A	N/A
2017/0174564	12/2016	Cleary et al.	N/A	N/A
2017/0197870	12/2016	Finkeldey et al.	N/A	N/A
2017/0226007	12/2016	Garner et al.	N/A	N/A
2017/0233287	12/2016	Li et al.	N/A	N/A
2017/0361574	12/2016	Kiczenski et al.	N/A	N/A
2018/0200955	12/2017	Hoelldorfer et al.	N/A	N/A
2018/0210308	12/2017	Lam et al.	N/A	N/A
2018/0250748	12/2017	Page	N/A	N/A
2018/0304588	12/2017	Harris et al.	N/A	N/A
2019/0022979	12/2018	Uzzato et al.	N/A	N/A
2019/0030861	12/2018	Bellman et al.	N/A	N/A
2019/0160787	12/2018	Bartlow et al.	N/A	N/A
2019/0161402	12/2018	Harris et al.	N/A	N/A
2019/0227357	12/2018	Williams et al.	N/A	N/A
2019/0270284	12/2018	Couillard et al.	N/A	N/A

2019/0391337	12/2018	Sato	N/A	N/A
2020/0039146	12/2019	Jahnle et al.	N/A	N/A
2022/0144682	12/2021	McIaren et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
42657/72	12/1972	AU	N/A
05245/73	12/1981	AU	N/A
05351/29	12/1983	AU	N/A
1148742	12/1982	CA	N/A
1176468	12/1983	CA	N/A
2171323	12/1995	CA	N/A
1208266	12/1998	CN	N/A
1501892	12/2003	CN	N/A
1693247	12/2004	CN	N/A
1896020	12/2006	CN	N/A
101312919	12/2007	CN	N/A
101671112	12/2009	CN	N/A
101774751	12/2009	CN	N/A
101801869	12/2009	CN	N/A
102112407	12/2010	CN	N/A
102149649	12/2010	CN	N/A
102503103	12/2011	CN	N/A
102574726	12/2011	CN	N/A
102659305	12/2011	CN	N/A
102863146	12/2012	CN	N/A
103201230	12/2012	CN	N/A
103253857	12/2012	CN	N/A
103319082	12/2012	CN	N/A
103359934	12/2012	CN	N/A
103534216	12/2013	CN	N/A
103781733	12/2013	CN	N/A
103827051	12/2013	CN	N/A
104103385	12/2013	CN	N/A
104144877	12/2013	CN	N/A
104211288	12/2013	CN	N/A
104260569	12/2014	CN	N/A
104295448	12/2014	CN	N/A
104310773	12/2014	CN	N/A
104355530	12/2014	CN	N/A
104364213	12/2014	CN	N/A
104379532	12/2014	CN	N/A
104428262	12/2014	CN	N/A
104479282	12/2014	CN	N/A
104520249	12/2014	CN	N/A
104541233	12/2014	CN	N/A
104583141	12/2014	CN	N/A
104619622	12/2014	CN	N/A
104619662	12/2014	CN	N/A

104781201	12/2014	CN	N/A
105271762	12/2015	CN	N/A
205275454	12/2015	CN	N/A
105980147	12/2015	CN	N/A
106045283	12/2015	CN	N/A
206970472	12/2017	CN	N/A
2233057	12/1972	DE	N/A
0173418	12/1985	EP	N/A
0413254	12/1990	EP	N/A
0426363	12/1990	EP	N/A
0441804	12/1990	EP	N/A
0882681	12/1997	EP	N/A
1215039	12/2001	EP	N/A
1245545	12/2001	EP	N/A
1380550	12/2003	EP	N/A
1414762	12/2003	EP	N/A
1533282	12/2004	EP	N/A
1925952	12/2007	EP	N/A
2543644	12/2012	EP	N/A
2782753	12/2013	EP	N/A
2819965	12/2014	EP	N/A
2853517	12/2014	EP	N/A
2876092	12/2014	EP	N/A
2326386	12/1976	FR	N/A
2936794	12/2009	FR	N/A
0996423	12/1964	GB	N/A
1026770	12/1965	GB	N/A
1103192	12/1967	GB	N/A
1112781	12/1967	GB	N/A
1160284	12/1968	GB	N/A
1253681	12/1970	GB	N/A
1282720	12/1971	GB	N/A
1289488	12/1971	GB	N/A
2232978	12/1990	GB	N/A
202420	12/2004	IN	N/A
200803022	12/2007	IN	N/A
201404365	12/2014	IN	N/A
201407444	12/2014	IN	N/A
51-103920	12/1975	JP	N/A
55-104935	12/1979	JP	N/A
56-155030	12/1980	JP	N/A
56-155031	12/1980	JP	N/A
57-067035	12/1981	JP	N/A
57-067036	12/1981	JP	N/A
58-088132	12/1982	JP	N/A
58-091042	12/1982	JP	N/A
59-008626	12/1983	JP	N/A
59-008627	12/1983	JP	N/A
59-008628	12/1983	JP	N/A
59-008629	12/1983	JP	N/A

59-008630	12/1983	JP	N/A
59-008631	12/1983	JP	N/A
59-057923	12/1983	JP	N/A
60-171245	12/1984	JP	N/A
61-072637	12/1985	JP	N/A
61-141756	12/1985	JP	N/A
62-036030	12/1986	JP	N/A
63-270330	12/1987	JP	N/A
02-102436	12/1989	JP	N/A
02-175624	12/1989	JP	N/A
03-045526	12/1990	JP	N/A
03-271127	12/1990	JP	N/A
05-098626	12/1992	JP	N/A
05-098627	12/1992	JP	N/A
05-098628	12/1992	JP	N/A
05-098629	12/1992	JP	N/A
05-098630	12/1992	JP	N/A
05-098631	12/1992	JP	N/A
05-330835	12/1992	JP	N/A
06-236030	12/1993	JP	N/A
06-336533	12/1993	JP	N/A
07-089739	12/1994	JP	N/A
07-809739	12/1994	JP	N/A
07-157322	12/1994	JP	N/A
07-267664	12/1994	JP	N/A
09-278468	12/1996	JP	N/A
09-301732	12/1996	JP	N/A
11-199257	12/1998	JP	N/A
11-310430	12/1998	JP	N/A
2000-072463	12/1999	JP	N/A
2000-103632	12/1999	JP	N/A
2000-172202	12/1999	JP	N/A
2000-327355	12/1999	JP	N/A
2001-002434	12/2000	JP	N/A
2001-180967	12/2000	JP	N/A
2001-307662	12/2000	JP	N/A
2001-348245	12/2000	JP	N/A
2003-040635	12/2002	JP	N/A
2003-137603	12/2002	JP	N/A
2003-261344	12/2002	JP	N/A
2003-321255	12/2002	JP	N/A
2003-342030	12/2002	JP	N/A
2004-091311	12/2003	JP	N/A
2004-115358	12/2003	JP	N/A
3804115	12/2005	JP	N/A
2006-298691	12/2005	JP	N/A
2007-191319	12/2006	JP	N/A
2007-261850	12/2006	JP	N/A
2008-282863	12/2007	JP	N/A
4397196	12/2009	JP	N/A

4438126	12/2009	JP	N/A
4557606	12/2009	JP	N/A
4642107	12/2010	JP	N/A
4722371	12/2010	JP	N/A
4951838	12/2011	JP	N/A
2012-232882	12/2011	JP	N/A
2013-177253	12/2012	JP	N/A
5334005	12/2012	JP	N/A
2014-001121	12/2013	JP	N/A
2014-073952	12/2013	JP	N/A
2014-521586	12/2013	JP	N/A
2014-166938	12/2013	JP	N/A
2014-523389	12/2013	JP	N/A
5614607	12/2013	JP	N/A
5622069	12/2013	JP	N/A
2015-006650	12/2014	JP	N/A
2015-034123	12/2014	JP	N/A
2015-054790	12/2014	JP	N/A
2015-061808	12/2014	JP	N/A
2015-086080	12/2014	JP	N/A
5714701	12/2014	JP	N/A
2015-112929	12/2014	JP	N/A
2015-151329	12/2014	JP	N/A
2015-163574	12/2014	JP	N/A
10-0218143	12/1998	KR	N/A
10-2002-0061567	12/2001	KR	N/A
10-0690381	12/2006	KR	N/A
10-0909835	12/2008	KR	N/A
10-0918577	12/2008	KR	N/A
10-0937889	12/2009	KR	N/A
10-1000677	12/2009	KR	N/A
10-1032825	12/2010	KR	N/A
10-2011-0087774	12/2010	KR	N/A
10-2011-0106629	12/2010	KR	N/A
10-2011-0112503	12/2010	KR	N/A
10-1093947	12/2010	KR	N/A
10-1120262	12/2011	KR	N/A
10-2012-0051220	12/2011	KR	N/A
10-2012-0070450	12/2011	KR	N/A
10-2013-0024484	12/2012	KR	N/A
10-1248380	12/2012	KR	N/A
10-1286131	12/2012	KR	N/A
10-1413626	12/2013	KR	N/A
2014-0095564	12/2013	KR	N/A
10-2014-0110364	12/2013	KR	N/A
10-2014-0135846	12/2013	KR	N/A
2015-0002816	12/2014	KR	N/A
2015-0013166	12/2014	KR	N/A
10-2015-0051166	12/2014	KR	N/A
10-2015-0129302	12/2014	KR	N/A

10-2015-0129703	12/2014	KR	N/A
2015-0129703	12/2014	KR	N/A
2151750	12/1999	RU	N/A
2199496	12/2002	RU	N/A
2237621	12/2003	RU	N/A
2299184	12/2006	RU	N/A
2464243	12/2011	RU	N/A
254731	12/2012	RU	N/A
95854	12/1951	SU	N/A
443845	12/1973	SU	N/A
537960	12/1975	SU	N/A
631464	12/1977	SU	N/A
556593	12/1981	SU	N/A
548188	12/1981	SU	N/A
1098916	12/1983	SU	N/A
1150234	12/1984	SU	N/A
1655920	12/1990	SU	N/A
201111317	12/2010	TW	N/A
201119967	12/2010	TW	N/A
1393686	12/2012	TW	N/A
201343590	12/2012	TW	N/A
201343591	12/2012	TW	N/A
201418174	12/2013	TW	N/A
201509858	12/2014	TW	N/A
201609589	12/2015	TW	N/A
201623168	12/2015	TW	N/A
90/03337	12/1989	WO	N/A
99/44952	12/1998	WO	N/A
01/16040	12/2000	WO	N/A
01/34531	12/2000	WO	N/A
02/16277	12/2001	WO	N/A
03/14035	12/2002	WO	N/A
2006/083902	12/2005	WO	N/A
2006/110145	12/2005	WO	N/A
2008/020509	12/2007	WO	N/A
2008/143999	12/2007	WO	N/A
2008/147558	12/2007	WO	N/A
2010/076903	12/2009	WO	N/A
2011/122678	12/2010	WO	N/A
2012/082709	12/2011	WO	N/A
2012/125857	12/2011	WO	N/A
2012/142629	12/2011	WO	N/A
2013/001841	12/2012	WO	N/A
2013/016157	12/2012	WO	N/A
2013/078039	12/2012	WO	N/A
2013/130665	12/2012	WO	N/A
2013/130700	12/2012	WO	N/A
2014/024583	12/2013	WO	N/A
2014/030682	12/2013	WO	N/A
2014/060108	12/2013	WO	N/A

2014/139147	12/2013	WO	N/A
2014/182641	12/2013	WO	N/A
2014/182776	12/2013	WO	N/A
2014/201315	12/2013	WO	N/A
2015/031148	12/2014	WO	N/A
2015/031594	12/2014	WO	N/A
2015/033562	12/2014	WO	N/A
2015/057552	12/2014	WO	N/A
2015/088010	12/2014	WO	N/A
2015/125584	12/2014	WO	N/A
2015/156262	12/2014	WO	N/A
2016/019171	12/2015	WO	N/A
2016/037793	12/2015	WO	N/A
2016/057590	12/2015	WO	N/A
2016/094262	12/2015	WO	N/A
2016/183059	12/2015	WO	N/A
2017/019837	12/2016	WO	N/A
2017/020041	12/2016	WO	N/A
2017/066243	12/2016	WO	N/A
2017/071911	12/2016	WO	N/A
2017/079540	12/2016	WO	N/A
2017/139552	12/2016	WO	N/A
2018/136384	12/2017	WO	N/A
2018/136388	12/2017	WO	N/A
2021/025981	12/2020	WO	N/A

OTHER PUBLICATIONS

Conway, Jr., Joseph C. et al., "Use of Crack Branching Data for Measuring Near-Surface Residual Stresses in empered Glass," Journal of the American Ceramic Society, vol. 72, No. 9, Sep. 1989, pp. 1584-1587. cited by applicant

Cox, Dr. Chris, "Lecture 3: Complex exponential function, Fourier and Laplace transforms," IMI-NFG's MITT Course on Relaxation Processes in Glass and Polymers Lecture 3, 2010, 25 slides. cited by applicant

Cox, Dr. Chris, "Lecture 4: Differential Equations," IMI-NFG's Min Course on Relaxation Processes in Glass and Polymers Lecture 4, 2010, 24 slides. cited by applicant

Danishkin, G. K. et al., "Development of a Continuous Method of Bending and Toughening Glass," Glass and Ceramics, vol. 34, Issue 8, Aug. 1977, pp. 495-498. cited by applicant

Daudeville, L. et al., "Numerical Simulation of Soda-Lime Silicate Glass Tempering," Journal de Physique IV, France, vol. 6, No. C1, Jan. 1996, pp. C1-175-C1-185. cited by applicant

Daudeville, Laurent et al., "Thermal Tempering Simulation of Glass Plates: Inner and Edge Residual Stresses," Journal of Thermal Stresses, vol. 21, 1998, pp. 667-689. cited by applicant

De Grauw, C. J. et al., "Axial resolution of confocal Raman microscopes: Gaussian beam theory and practice," Journal of Microscopy, vol. 188, Pt. 3, Dec. 1997, pp. 273-279. cited by applicant

Deschamps, T. et al., "Soda-lime silicate glass under hydrostatic pressure and indentation: a micro-Raman study," Abstract, 2011, 1 page. cited by applicant

Donald, I. W., "Review: Methods for improving the mechanical properties of oxide glasses," Journal of Materials Science, vol. 24, 1989, pp. 4177-4208. cited by applicant

Dr. Tallant, T.A. Michalske, and W.L. Smith, "The effects of tensile stress on the Raman spectrum of silica glass," J. Non-Cryst. Solids, 106 380-383 (1988). cited by applicant

Electronic Cooling Editors, "The Thermal Conductivity of Gases", Design, Materials, Adhesives,

Substrates, No. 3, Technical Data, Test & Measurement, vol. 4, Gases, Thermal Conductivity, Sep. 1, 1998, 2 pages. cited by applicant

English Translation of CN104211288A, Performed by Phoenix Translations Jun. 2016. cited by applicant

Ernsberger, F. M., "Chapter 1: Elastic Properties of Glasses," In "Glass: Science and Technology," vol. 5, Elasticity and Strength in Glasses, Academic Press, Inc., May 28, 1980, pp. 1-19. cited by applicant

Ernsberger, F. M., "Chapter 4: Techniques of Strengthening Glasses," In "Glass: Science and Technology," vol. 5, Elasticity and Strength in Glasses, Academic Press, Inc., May 28, 1980, pp. 133-144. cited by applicant

Europtec; "Thermal Tempering" ; Europtec GMBH, DIC, Jun. 11, 2014; www.europtec.de. cited by applicant

Everall, Neil et al., "Optimizing Depth Resolution in Confocal Raman Microscopy: A Comparison of Metallurgical, Dry Corrected, and Oil Immersion Objectives," Applied Spectroscopy, vol. 61, No. 3, 2007, pp. 251-259. cited by applicant

Everall, Neil J., "Confocal Raman Microscopy: Why the Depth Resolution and Spatial Accuracy Can Be Much Worse than You Think," Applied Spectroscopy, vol. 54, No. 10, 2000, pp. 1515-1520. cited by applicant

Fajans, Kasimir et al., "Properties and Structures of Vitreous and Crystalline Boron Oxide," Journal of the American Chemical Society, vol. 74, No. 11, Jun. 5, 1952, pp. 2761-2768. cited by applicant

Fotheringham, Dr. Ulrich, "Lecture 1: Internet teaching set-up," IMI-NFG's MITT Course on Relaxation Processes in Glass and Polymers Lecture 1, 2010, 6 slides. cited by applicant

Fotheringham, Dr. Ulrich, "Lecture 2: Phenomenology of viscoelasticity & glass transition," IMI-NFG's MITT Course on Relaxation Processes in Glass and Polymers Lecture 2, 2010, 17 slides. cited by applicant

Fotheringham, Dr. Ulrich, "Lecture 5: Viscoelasticity I—Shear," IMI-NFG's MITI Course on Relaxation Processes in Glass and Polymers Lecture 5, 2010, 19 slides. cited by applicant

Fotheringham, Dr. Ulrich, "Lecture 6: Viscoelasticity II—Bulk Viscoelasticity," IMI-NFG's MITI Course on Relaxation Processes in Glass and Polymers Lecture 6, 2010, 16 slides. cited by applicant

Fotheringham, Dr. Ulrich, "Lecture 7: Viscoelasticity III—Dynamic Testing," IMI-NFG's MITT Course on Relaxation Processes in Glass and Polymers Lecture 7, 2010, 19 slides. cited by applicant

Fotheringham, Dr. Ulrich, "Lecture 8: Viscoelasticity IV—Important Application of Pre-Stressing," IMI-NFG's MITT Course on Relaxation Processes in Glass and Polymers Lecture 8, 2010, 12 slides. cited by applicant

Freiman, S. W., "Chapter 2: Fracture Mechanics of Glass," In "Glass: Science and Technology," vol. 5, Elasticity and Strength in Glasses, Academic Press, Inc., May 28, 1980, pp. 21-78. cited by applicant

Frick, B. et al., "The Microscopic Basis of the Glass Transition in Polymers from Neutron Scattering Studies," Science, vol. 267, Mar. 31, 1995, pp. 1939-1945. cited by applicant

Galeener, Frank L., "Raman and ESR Studies of the Thermal History of Amorphous SiO₂," Journal of Non-Crystalline Solids, vol. 71, 1985, pp. 373-386. cited by applicant

Gammelgaard et al., "Graphene transport properties upon exposure to PMMA processing and heat treatments", 2D Materials, vol. 1, 2014, 035005, 12 pages. cited by applicant

Gang, Zhang Ming, "Manufacturing and Properties of Glass Used in Construction," Guangdong Golden Glass Technologies Ltd, Dec. 27, 2002, 11 pages. cited by applicant

Gao, "Glass weathering and methods for preventing it," Wuhan University of Technology Press, Dec. 31, 1995, 5 pages (Translation Attached. cited by applicant

Gardon, Robert, "Calculation of Temperature Distributions in Glass Plates Undergoing Heat-

Treatment,” Journal of the American Ceramic Society, vol. 41, No. 6, Jun. 1958, pp. 200-209. cited by applicant

Gardon, Robert, “Chapter 5: Thermal Tempering of Glass,” In “Glass: Science and Technology,” vol. 5, Elasticity and Strength in Glasses, Academic Press, Inc., May 28, 1980, pp. 145-216. cited by applicant

Gardon, Robert, “Tempering Glass with Modulated Cooling Schedules,” Journal of the American Ceramic Society, vol. 71, No. 10, Oct. 1988, pp. 876-878. cited by applicant

Gardon, Robert, “Variation of Densities and Refractive Indices in Tempered Glass,” Journal of the American Ceramic Society, vol. 61, No. 3-4, Mar.-Apr. 1978, pp. 143-146. cited by applicant

Gardon; “Thermal Tempering of Glass”; pp. 146-216 In Glass: Science and Technology, vol. 5, Elasticity and Strength in Glasses, Ed. by D.R. Uhlmann and N.J. Kreidl, Academic Press, New York, 1980. cited by applicant

Glass Unlimited “AGC Technical Data Sheet Planibel”. ; Nov. 2011 (Year: 2011). cited by applicant

Glass, Jill et al., “Processing and Properties of Ion Exchanged Glasses,” Glass and Optical Materials Division Fall Meeting, Nov. 6-12, 2004, Cape Canaveral, FL, 33 slides. cited by applicant

Glass, S. J. et al., “Stressed Glass Technology for Actuators and Removable Barrier Applications,” Sandia Report SAND2007-4106, Sandia National Laboratories, Jul. 2007, 18 pages. cited by applicant

Global Dossier Translation of JP 2018-504918 Office Action Dated Jul. 15, 2020; 2 Pages; Japanese Patent Office. cited by applicant

Gomez, Sinue et al., “69.2: Designing Strong Glass for Mobile Devices,” SID Symposium Digest of Technical Papers, vol. 40, No. 1, Jan. 2009, pp. 1045-1048. cited by applicant

Gross et al. “A glass with high crack initiation load: Role of fictive temperature-independent mechanical properties”; Journal of Non-crystalline Solids 355 (2009) pp. 563-568 (Year: 2009). cited by applicant

Gross, T.M., “Deformation and cracking behavior of glasses indented with diamond tips of various sharpness,” Journal of Non-Crystalline Solids, vol. 358, Issue 24, Dec. 12, 2012, pp. 3445-3452. cited by applicant

Guillemet, C., “Annealing and Tempering of Glass,” Journal of Non-Crystalline Solids, vol. 123, 1990, pp. 415-426. cited by applicant

Gulati, “Frangibility of Tempered Soda-Lime Glass Sheet,” pp. 13-15 in Glass Performance Days, 1997. cited by applicant

Guo, Xiaojun et al. “Unified approach for determining the enthalpic fictive temperature of glasses with arbitrary thermal history” Journal of Non-Crystalline Solids, vol. 357, 2011, pp. 3230-3236. cited by applicant

Gupta, Prabhat K. et al., “The laboratory glass transition,” The Journal of Chemical Physics, vol. 126, 2007, 9 pages. cited by applicant

Gupta, Prabhat, “Landscape Approach to Glass Transition and Relaxation: Basic Concepts (contd.),” IMI-NFG's MITT Course on Relaxation Processes in Glass Lecture 18, Mar. 25, 2010, 23 slides. cited by applicant

Gupta, Prabhat, “Landscape Approach to Glass Transition and Relaxation: Four lectures on ‘The Landscape Approach,’” IMI-NFG's MITT Course on Relaxation Processes in Glass Lecture 17, Mar. 23, 2010, 28 slides. cited by applicant

Gupta, Prabhat, “Landscape Approach to Glass Transition and Relaxation: Liquid to Glass Transition,” IMI-NFG's MITT Course on Relaxation Processes in Glass Lecture 19, Mar. 30, 2010, 25 slides. cited by applicant

Gupta, Prabhat, “Landscape Approach to Glass Transition and Relaxation: Relaxation in the glassy state,” IMI- NFG's Min Course on Relaxation Processes in Glass Lecture 20, Apr. 1, 2010, 20

slides. cited by applicant

Gy, Rene, "Ion exchange for glass strengthening," *Materials Science and Engineering B*, vol. 149, 2008, pp. 159-165. cited by applicant

Hara, Morihisa et al., "Vickers Hardness of Toughened Sheet Glass," *Reports of the Research Laboratory, Asahi Glass Co., Ltd.*, vol. 12, No. 2, 1962, pp. 99-104. cited by applicant

Hibino, Yoshinori et al., "Raman study on silica optical fibers subjected to high tensile stress," *Applied Physics Letters*, vol. 47, No. 8, Oct. 15, 1985, pp. 812-814. cited by applicant

Hodge, Ian M., "Physical Aging in Polymer Glasses," *Science*, vol. 267, No. 5206, Mar. 31, 1995, pp. 1945-1947. cited by applicant

Hrma et al; "Thermal Healing of Cracks in Glass"; *Journal of Non-Crystalline Solids*; vol. 102, (1988); pp. 88-94. cited by applicant

Huang, Liping et al., "Polyamorphic transitions in vitreous B₂O₃ under pressure," *Journal of Physics: Condensed Matter*, vol. 20, 2008, 8 pages. cited by applicant

Hubert, Mathieu, "Lecture 9: Annealing and tempering," IMI-NFG Course on Processing in Glass—Lecture 9, Feb. 19, 2015, 72 slides. cited by applicant

Hutchins, J. and R. Harrington, "Glass", *Kirk-Othmer Encyclopedia of Chemical Technology*, 2nd Edition, vol. 10, 1966, pp. 533-604. cited by applicant

Ito, Setsuro, "Brittleness and Nano-Structure of Glass," 4th International Workshop on Flow and Fracture of Advanced Glasses Presentation, Nov. 5-7, 2007, Shiga, Japan, 37 slides. cited by applicant

Jain, Himanshu, "Electrical Relaxation—Topic 1: Quasi-free ion transport," IMI-NFG's MITI Course on Relaxation Processes in Glass Lecture 23, Advanced Vitreous State, The Properties of Glass: Dielectric Properties—Lecture 1, 2010, 28 slides. cited by applicant

Jain, Himanshu, "Electrical Relaxation—Topic 3: Nearly constant loss—second universality," IMI-NFG's Min Course on Relaxation Processes in Glass Lecture 25, Advanced Vitreous State, The Properties of Glass: Dielectric Properties—Lecture 3, 2010, 24 slides. cited by applicant

John Klein et al: "Additive Manufacturing of optically Transparent Glass", *3D Printing and Additive Manufacturing*, vol. 2, No. 3, Aug. 19, 2015 (Aug. 19, 2015), pp. 92-105, XP055328426. cited by applicant

Karlsson, Stefan et al., "The technology of chemical glass strengthening—a review," *Glass Technology, European Journal of Glass Science Technology Part A*, vol. 51, No. 2, Apr. 2010, pp. 41-54. cited by applicant

Kassir-Bodon, Assia et al., "Raman Mapping of the Indentation-Induced Densification of a Soda-Lime-Silicate Glass," *International Journal of Applied Glass Science*, vol. 3, No. 1, 2012, pp. 29-35. cited by applicant

Kiefer, Werner et al., "Method for Thermal Prestressing of Glass," *Strength of Inorganic Glass*, Plenum Press, New York, 1985, pp. 501-511. cited by applicant

Kishii, Toru, "Surface Stress Meters Utilising the Optical Waveguide Effect of Chemically Tempered Glasses," *Optics and Lasers in Engineering*, vol. 4, 1983, pp. 25-38. cited by applicant

Kistler, S. S., "Stresses in Glass Produced by Nonuniform Exchange of Monovalent Ions," *Journal of the American Ceramic Society*, vol. 45, No. 2, Feb. 1962, pp. 59-68. cited by applicant

Koike et al.—Sub-critical crack growth rate of soda-lime-silicate glass and less brittle glass as a function of fictive temperature; *Journal of Non-Crystalline Solids* vol. 353 Issue 27 pp. 2675-2680; Jun. 2007 (Year: 2007). cited by applicant

Koike, A. et al., "Fictive temperature dependence of subcritical crack growth rate of normal glass and anomalous glass," *Journal of Non-Crystalline Solids*, vol. 352, 2006, pp. 5522-5530. cited by applicant

Kong, Jinhak et al., "Residual Stress Analysis with Improved Numerical Methods for Tempered Plate Glasses Based on Structural Relaxation Model," *Metals and Materials International*, vol. 13, No. 1, 2007, pp. 67-75. cited by applicant

Lathabai, Srinivasarao et al., “Fracture mechanics model for subthreshold indentation flaws: Part 1—Equilibrium fracture,” *Journal of Materials Science*, vol. 26, 1991, pp. 2157-2168. cited by applicant

Lee, Hoikwan et al., “Glass Thickness and Fragmentation Behavior in Stressed Glasses,” *New Journal of Glass and Ceramics*, vol. 2, 2012, pp. 138-143. cited by applicant

Lezzi, P. J. et al., “Confirmation of thin surface residual compressive stress in silica glass fiber by FTIR reflection spectroscopy,” *Journal of Non-Crystalline Solids*, vol. 390, 2014, pp. 13-18. cited by applicant

Li, Hong et al., “Effect of Fictive Temperature on Dynamic Fatigue Behavior of Silica and Soda-Lime Glasses,” *Journal of the American Ceramic Society*, vol. 78, No. 5, 1995, pp. 1393-1396. cited by applicant

Lin et al., “Graphene annealing: how clean can it be?,” *Nano Lett.*, vol. 12, Issue 1, 2012, pp. 414-419. cited by applicant

Loucks, “Lecture 13: The Fictive and Glass Transition Temperatures,” IMI-NFG's Min Course on Relaxation Processes in Glass Lecture 13, Mar. 2, 2010, 25 Slides. cited by applicant

Loucks, “Lecture 14: Relaxation and the Tool-Narayanaswamy-Moynihan Equation,” IMI-NFG's MITT Course on Relaxation Processes in Glass Lecture 14, Mar. 4, 2010, 27 Slides. cited by applicant

Loucks, “Lecture 15: The Tool-Narayanaswamy-Moynihan Equation Part II and DSC,” IMI-NFG's MITT Course on Relaxation Processes in Glass Lecture 15, Mar. 9, 2010, 33 Slides. cited by applicant

Luo et al., “Competing Indentation Deformation Mechanisms in Glass Using Different Strengthening Methods”, *Frontiers in Materials*, vol. 3, No. 52, 2016, 11 pages. cited by applicant

Luo et al; “Additive Manufacturing of Glass for Optical Applications”; *Proc. of SPIE*, vol. 9738, 2016; pp. 97380Y-1-97380Y-9. cited by applicant

Markovsky, Alex et al., “An Efficient and Stable Algorithm for Calculating Fictive Temperatures,” *Communications of the American Ceramic Society*, Apr. 1984, 2 pages. cited by applicant

Martin, Dr. Steve, “Lecture 10: Thermodynamic Functions,” IMI-NFG's MITT Course on Relaxation Processes in Glass Lecture 10, 2010, 25 slides. cited by applicant

Martin, Dr. Steve, “Lecture 11: Thermodynamics in the Glass Transition Region,” IMI-NFG's MITT Course on Relaxation Processes in Glass Lecture 11, 2010, 22 slides. cited by applicant

Martin, Dr. Steve, “Lecture 12: The Glass Transition as a Kinetic Transition,” IMI-NFG's Min Course on Relaxation Processes in Glass Lecture 12, 2010, 21 slides. cited by applicant

Martin, Dr. Steve, “Lecture 9: Thermodynamic Concepts and the Law of Thermodynamics,” IMI-NFG's Min Course on Relaxation Processes in Glass Lecture 9, 2010, 32 slides. cited by applicant

Massen, Claire P. et al., “Power-law distributions for the areas of the basins of attraction on a potential energy landscape,” *Physical Review E*, The American Physical Society, vol. 75, 2007, 4 pages. cited by applicant

Mauricio-Iglesias, M. et al., “Raman depth-profiling characterization of a migrant diffusion in a polymer,” *Journal of Membrane Science*, vol. 375, 2011, pp. 165-171. cited by applicant

McGlinchy, Timothy B., “Energy Efficient Triple IG Automation EEE (Triple-E),” DE-EE0000167, GED Integrated Solutions, Feb. 28, 2013, 45 pages. cited by applicant

McMaster, Ronald A. et al., “Annealed and Tempered Glass,” *Engineered Materials Handbook*, vol. 4, Ceramics and Glasses, 1991, 9 pages. cited by applicant

McMaster, Ronald A., “Flat Glass Tempering—How It Works,” *Glass Industry*, Jun. 1989, pp. 10-15. cited by applicant

McMaster, Ronald A., “Fundamentals of Tempered Glass,” *Proceedings of the 49th Conference on Glass Problems: Ceramic Engineering and Science Proceedings*, vol. 10, Issue 3/4, 1989, pp. 193-206. cited by applicant

Merriam-Webster Online Dictionary, “Coextensive” , 2009, 1 page. Retrieved from:

<https://www.merriam-webster.com/dictionary/coextensive>. cited by applicant

Mikowski, A. et al., "Statistical analysis of threshold load for radial crack nucleation by Vickers indentation in commercial soda-lime silica glass," *Journal of Non-Crystalline Solids*, vol. 352, 2006, pp. 3544-3549. cited by applicant

Mognato, Ennio et al., "Thermally toughened safety glass," *Glass on Web*, Last Reviewed: Jul. 2011, 9 pages, <http://www.glassonweb.com/articles/article/727/>. cited by applicant

Morey; "The Effect of Boric Oxide on the Devitrification of the Soda-Lime-Silica Glasses. The Quaternary System, $\text{Na}_2\text{O}-\text{CaO}-\text{B}_2\text{O}_3-\text{SiO}_2$ "; *Journal of the American Ceramic Society*; vol. 15, Issue 9; pp. 457-475 (1932). cited by applicant

Moynihan, C. T. et al., "Structural Relaxation in Vitreous Materials," *Annals of the New York Academic of Sciences*, vol. 279, Oct. 1976, pp. 15-35. cited by applicant

Narayanaswamy, O. S. et al., "Calculation of Residual Stresses in Glass," *Journal of the American Ceramic Society*, vol. 52, No. 10, Oct. 1969, pp. 554-558. cited by applicant

Narayanaswamy; "Stress and Structural Relaxation in Tempering Glass," *J. Am. Ceram. Soc.*, 61[3-4] 146-152 (1978). cited by applicant

Oakley, David R., "Crack branching in float glass subjected to biaxial loading," *Journal of Non-Crystalline Solids*, vol. 196, 1996, pp. 139-143. cited by applicant

Ohlberg, S.M. et al., "Thermal Stress Calculations Based on a Linear Viscoelastic Deviatoric Response and a Fictive Temperature Component for the Volumetric Response," *Journal of Non-Crystalline Solids*, vol. 14, 1974, pp. 280-286. cited by applicant

Paschel, Richard, "History of the Safety Glazing Certification Council," *Safety Glazing Certification Council*, 1971, 11 pages. cited by applicant

Properties of Soda-Lime Silica Float Glass Technical Bulletin; NSG; Group; Pilkington North America, Inc. Jan. 14, 2013 (Year: 2013). cited by applicant

Ray, N. H. et al., "Increasing the strength of glass by treatment in molten salts," *Physics and Chemistry of Glasses*, vol. 8, No. 1, Feb. 1967, pp. 30-34. cited by applicant

Rekhson, S. M., "Chapter 1: Viscoelasticity of Glass," In "Glass: Science and Technology," vol. 3, 1986, 117 pages. cited by applicant

Rekson, S. M., "Structural Relaxation and Shear Stresses in the Glass-Transition Region," *Soviet Journal of Glass Physics and Chemistry*, 1975, pp. 417-421. cited by applicant

Sastry, Srikanth, "The relationship between fragility, configurational entropy and the potential energy landscape of glass-forming liquids," *Nature*, vol. 409, Jan. 11, 2001, pp. 164-167. cited by applicant

Scherer, George W., "Use of the Adam-Gibbs Equation in the Analysis of Structural Relaxation," *Journal of the American Ceramic Society*, vol. 67, No. 7, Jul. 1984, pp. 504-511. cited by applicant

Sciortino, Francesco, "Potential energy landscape description of supercooled liquids and glasses," *Journal of Statistical Mechanics: Theory and Experiment*, May 31, 2005, 35 pages. cited by applicant

Sehgal, Jeetendra et al., "A New Low-Brittleness Glass in the Soda-Lime-Silica Glass Family," *Journal of the American Ceramic Society*, vol. 81, No. 9, Sep. 1998, pp. 2485-2488. cited by applicant

Setsuro, Ito et al., "Processing Technical Books to the Glass High-Functions," Chapter 3: Sections 2.5, 3, 3.1, 3.2 & 3.3, Science & Technology Co., Ltd., Sep. 27, 2012, pp. 58-65. cited by applicant

Sglavo, V., A. Prezzi, M. Alessandrini, "Processing of Glasses with Engineered Stress Profiles," *Journal of Non-Crystalline Solids*, 344 (2004), 73-78. cited by applicant

Shelby "Introduction to Glass Science and Technology"; The Royal Chemical Society, 2nd Edition, 2005; p. 193. cited by applicant

Shimodaira, N. et al., "Raman spectra of fluorine-doped silica glasses with various fictive temperatures," *Journal of Applied Physics*, vol. 91, No. 6, Mar. 15, 2002, pp. 3522-3525. cited by applicant

Shinkai, Norihiko et al., "Indentation Fracture of Tempered Glasses," Reports of the Research Laboratory, Asahi Glass Co., Ltd., vol. 23, No. 2, 1973, pp. 83-99. cited by applicant

Shouyuan, Zhai et al., "Influence of Temperature and Time on Glass Strength During Chemical Tempering," Journal of Shangdong Institute of Light Industry (Natural Science Edition), Feb. 1996, 3 pages. cited by applicant

Shutov, A. I. et al., "Prediction of the Character of Tempered Glass Fracture," Glass and Ceramics, vol. 55, Nos. 1-2, 1998, pp. 8-10. cited by applicant

Soules, Thomas F. et al., "Finite-Element Calculation of Stresses in Glass Parts Undergoing Viscous Relaxation," Journal of the American Ceramic Society, vol. 70, No. 2, Feb. 1987, pp. 90-95. cited by applicant

Southard, J. C., "The Thermal Properties of Crystalline and Glassy Boron Trioxide," Journal of the American Chemical Society, vol. 63, No. 11, Nov. 1941, pp. 3147-3150. cited by applicant

Spaght, Monroe E. et al., "Studies on Glass. VIII. The Coefficient of Thermal Expansion of Boron Trioxide," Journal of Physical Chemistry, vol. 38, No. 1, 1934, pp. 103-110. cited by applicant

Specialty Glass Products, "Soda Lime/AR/Flint Glass"; <http://www.sgpinc.com/sodalime.htm> accessed Aug. 11, 2016. cited by applicant

Stillinger, Frank H. et al., "Packing Structures and Transitions in Liquids and Solids," Science, New Series, vol. 225, No. 4666, Sep. 7, 1984, pp. 983-989. cited by applicant

Stillinger, Frank H., "A Topographic View of Supercooled Liquids and Glass Formation," Science, New Series, vol. 267, No. 5206, Mar. 31, 1995, pp. 1935-1939. cited by applicant

Tallant, D. R. et al., "The Effects of Tensile Stress on the Raman Spectrum of the Silica Glass," Journal of Non-Crystalline Solids, vol. 106, 1988, pp. 380-383. cited by applicant

Tandon, Rajan et al., "Controlling the Fragmentation Behavior of Stressed Glass," Fracture Mechanics of Ceramics, vol. 14, 2005, pp. 77. cited by applicant

Timoshenko et al; "Theory of Elasticity"; 2nd Ed; p. 146. McGraw-Hill Book Co., New York, 1951. cited by applicant

To, Q.D., et al., "Failure analysis of tempered glass structures with pin-loaded joints," Engineering Failure Analysis, vol. 14, Issue 5, Jul. 2007, pp. 841-850. cited by applicant

Tomlinson, R., G. Calvert, and A. Conway, "A Photoelastic Investigation Into Spontaneous Glass Fracture", Proceedings of the XIth International Congress and Exposition, (Jun. 2008) 8 pgs. cited by applicant

Varughese, Binoy et al., "Effect of fictive temperature on mechanical strength of soda-lime glasses," Journal of Non-Crystalline Solids, vol. 241, 1998, pp. 134-139. cited by applicant

Walrafen, G. E. et al., "Raman investigation of optical Abers under high tensile stress," Journal of Applied Physics, vol. 52, No. 4, Apr. 1981, pp. 2832-2836. cited by applicant

Wang et al; "Glass and Hot Extrusion by Me Module for 3D Additive Manufacturing"; IEEE, 2016; pp. 1167-1171. cited by applicant

Wang, Fei et al., "Pressure Raman effects and internal stress in network glasses," Physical Review B, vol. 71, 2005, 32 pages. cited by applicant

Weissmann, Rand D. Durkop, "A Novel Method for Measuring Stresses in Flat Glass", XV International Congress on Glass Leningrad 1989, Proceeding 3b, O. V. Mazurin, ed., pp. 217-220. cited by applicant

WO-2016037793-A1—Bib Dta (Year: 2016). cited by applicant

Yamane, Masayuki, "Chapter 3: Thermal Processing," Glass Engineering Handbook, Asakura Publishing Co. Ltd., Jul. 1999, pp. 410-417. cited by applicant

Young Modulus of the elements; Wolfram Research Inc.; <http://periodictable.com/Properties/A/YoungModulus.v.html>; printed Mar. 7, 2019 (Year: 2019). cited by applicant

Yue, Y.Z. et al., "Determination of the Active temperature for a hyperquenched glass," Chemical Physics Letters, vol. 357, Issues 1-2, May 3, 2002, pp. 20-24. cited by applicant

Zaccaria et al.; "Thermal Healing of Realistic Flaws in Glass"; J. Mater. Civ. Eng 2016, 28(2); pp. 04015127-1-04015127-9. cited by applicant

Zaman, F. D. et al., "Cooling of a Plate with General Boundary Conditions," International Journal of Mathematics and Mathematical Sciences, vol. 23, No. 7, 2000, pp. 477-485. cited by applicant

Zhi-hai, L., "Development status and trend of tempered glass," Glass, Apr. 30, 2004, pp. 49-52 (Original Document Only). cited by applicant

"Effects of ion exchange on the Young's modulus of glass"; John D. Mackenzie, J. Wakaki; Journal of Non-crystalline Solids; vols. 38-39, Part 1 May-Jun. 1980, pp. 385-390 (Year: 1980). cited by applicant

"Energy Curable Resins", <https://www.allnex.com/en/technologies/energy-curable-resins>; retrieved on Oct. 10, 2022. cited by applicant

Aben, H. et al., "2.7 Stresses Due to Heterogeneities," Photoelasticity of Glass, Springer-Verlag, New York, 1993, 260 pages. cited by applicant

Acloque, P., "Influence of Strain-Systems in Glass upon the Course of its Fracture," Proceedings of the 4th International Glass Congress, vol. 6, 1965, pp. 279-291. cited by applicant

Acloque, Paul, "Comparison Between Heat-Transfer Conditions and Setting Up of Strain in Glass During Heat-Treatment," Journal of the American Ceramic Society, vol. 44, No. 7, Jul. 1961, pp. 364-373. cited by applicant

Agarwal, Anand et al., "A simple IR spectroscopic method for determining fictive temperature of silica glasses," Journal of Non-Crystalline Solids, vol. 185, 1995, pp. 191-198. cited by applicant

Agarwal, Anand et al., "Determination of Fictive Temperature of Soda-Lime Silicate Glass," Journal of the American Ceramic Society, vol. 78, No. 3, Mar. 1995, pp. 827-829. cited by applicant

Akeyoshi, K. et al., "Mechanical Properties of Tempered Glass," Proceedings of the 7th International Glass Congress, vol. 14, 1965, pp. 80-85. cited by applicant

Alexiades, V. et al., "The New Way/Glaston Problem," 28th Annual Workshop on Mathematical Problems in Industry, University of Delaware, Jun. 2012, 30 slides. cited by applicant

Argon, A. S., "Chapter 3: Inelastic Deformation and Fracture in Oxide, Metallic, and Polymeric Glasses," In, "Glass: Science and Technology," vol. 5, Elasticity and Strength in Glass, Academic Press, May 28, 1980, pp. 79-132. cited by applicant

Aronen, Antti et al., "Tempering of Thin Glass," Glasstec 2012: Engineered Transparency, Oct. 25-26, 2012, pp. 145-153. cited by applicant

ASTM C1499-09, "Standard Test Method for Monotonic Equibiaxial Flexural Strength of Advanced Ceramics at Ambient Temperature", 2013, 14 pages. cited by applicant

ASTM C158-02, "Standard Test Methods for Strength of Glass by Flexure" (Determination of Modulus of Rupture), 2012, 9 pages. cited by applicant

Author Unknown, "Application Note AN 527: Depth profiling of complex samples using confocal Raman microscopy," Bruker Optics Inc., 2012, 3 pages. cited by applicant

Author Unknown, "Architectural ERH2 ," Architectural Glass Systems, Glasstech, Inc., 2011, 2 pages. cited by applicant

Author Unknown, "Architectural FCH2(Trademark) ," Architectural Glass Systems, Glasstech, Inc., 2011, 2 pages. cited by applicant

Author Unknown, "Coming(Registered) Gorilla(Trademark) Glass," Corning Incorporated, 2009, 2 pages. cited by applicant

Author Unknown, "Glass Strengthening Methods," Abrisa Technologies, Apr. 2015, 2 pages. cited by applicant

Author Unknown, "Heat Treated Glass for Architectural Glazing," Glass Technical Document: TD-138, PPG Glass Technology, PPG Industries, Inc., Nov. 2011, 8 pages. cited by applicant

Author Unknown, "Introducing—Glasstech CRB-S.TM. 1900 for Solar Parabolic Shapes," Solar Glass Systems, Glasstech, Inc., Date Unknown, 1 page, Retrieved Jul. 1, 2015. cited by applicant

Author Unknown, "New Way Air Bearings," 28th Annual Workshop on Mathematical Problems in Industry, University of Delaware, Jun. 2012, 16 slides. cited by applicant

Author Unknown, "Products, Glazing Techniques and Maintenance Section 4: GGF Dalasheet for the Quality of Thermally Toughened Soda Lime Silicate Safety Glass for Building," Glass and Glazing Federation, Aug. 2009, 12 pages. cited by applicant

Author Unknown, "Schott Technical Glasses—Physical and technical properties," Schott North America, Inc., Feb. 2010, 44 pages. cited by applicant

Author Unknown, "scratch and dig numbers," Sizes, Inc., Last Revised: Jun. 24, 2010, 5 pages, http://fwww.sizes.com/units/scratch_and_dig.htm. cited by applicant

Author Unknown, "Solar FCH-S(Trademark) ," Solar Glass Systems, Glasstech, Inc., 2011, 2 pages. cited by applicant

Author Unknown, "Standard Specification for Heat-Strengthened and Fully Tempered Flat Glass," Designation: C 1048-12, ASTM International Standard, 2015, 7 pages. cited by applicant

Author Unknown, "Standard Specification for Heat-Treated Flat Glass—Kind HS, Kind FT Coated and Uncoated Glass," Designation: C 1048-4, ASTM International Standard, 2009, 7 pages. cited by applicant

Author Unknown, "Subject Index," Date Unknown, pp. 277-282. Retrieved Apr. 24, 2015. cited by applicant

Author Unknown, "Tempered Glass," Tecnoglass, www.tecnoglass.com/tempered.pdf, Date Unknown, 5 pages, Retrieved Jul. 28, 2015. cited by applicant

Author Unknown, "Thermal Tempering," EuropTec GmbH, Nov. 6, 2014, 2 pages. cited by applicant

Author Unknown, "Unsteady Heat Transfer—HT3: Experimental Studies of Thermal Diffusivities and Heat Transfer Coefficients," Date Unknown, 27 slides, Retrieved Jul. 21, 2015. cited by applicant

Ayinder, C.C. et al., "Thermal-Tempering Analysis of Bulk Metallic Glass Plates Using an Instant-Freezing Model," Metallurgical and Materials Transactions A, vol. 32A, Nov. 2001, pp. 2709-2715. cited by applicant

Baldwin, K. J. et al., "Confocal Raman Microspectroscopy through a Planar Interface," Applied Spectroscopy, vol. 55, No. 5, 2001, pp. 517-524. cited by applicant

Bandyopadhyay et al; "Application of Fused Deposition in Controlled Microstructure Metal-Ceramic Composites", Rapid Prototyping Journal, vol. 12 Issue 3, pp. 121 128 (2006). cited by applicant

Barr, J. W., "Glass Tempering by Numbers," Aug. 2008, 8 pages. cited by applicant

Barr, Jonathan W., "The Tempering Process," Cardinal Waxachachie Tempering Seminar, Mar. 26, 2008, 36 slides. cited by applicant

Barr, Jonathan, "The Glass Tempering Handbook—Understanding the Glass Tempering Process," Self Published, 2015, 52 pages, <http://www.lambertgtservices.co.uk/book/TheGlassTemperingHandbook.pdf>. cited by applicant

Barsom, John M., "Fracture of Tempered Glass," Journal of the American Ceramic Society, vol. 51, No. 2, Feb. 1968, pp. 75-78. cited by applicant

Bartholomew, Roger F. et al., "Chapter 6: Chemical Strengthening of Glass," In "Glass: Science and Technology," vol. 5, Elasticity and Strength in Glass, Academic Press, May 28, 1980, pp. 217-270. cited by applicant

Beauchamp, Edwin K. et al., "Dynamics of Window Glass Fracture in Explosions," Sandia Report SAND98-0598 UC-700, Sandia National Laboratories, May 1998, 74 pages. cited by applicant

Bird, R. D., W. E. Stewart, and E. N. Lightfoot, Transport Phenomena—Chapter 11: The Equations of Change for Nonisothermal Systems, Wiley, (1960) pp. 349-373. cited by applicant

Bird, R. D., W. E. Stewart, and E. N. Lightfoot, Transport Phenomena—Chapter 3: The Equations of Change for Isothermal Systems, Wiley, (1960) pp. 75-113. cited by applicant

Boaz, Prem, "Tempering Very Thin Glass-What Radio Waves Mean for the Glass Industry," USGlass Magazine, vol. 45, Issue 3, Mar. 2010, 5 pages. cited by applicant

Boaz, Prem, "Thin glass processing with radio wave assist," Glass on Web, Last Reviewed: Jan. 2013, 6 pages, <http://www.glassonweb.com/articles/article/561/>. cited by applicant

Boguslavskii, I. A., "Studying the Nature of the Super-Strength of Glasses Strengthened by the Thermophysical Method," Glass and Ceramics, vol. 21, No. 10, Oct. 1964, pp. 562-567. cited by applicant

Brown, Angus M., "Nonlinear regression analysis of data using a spreadsheet," Application Note, ISC, Oct. 2001, pp. 58-59. cited by applicant

Chen, et al., "Nanopatterned Graphene on a Polymer Substrate by a Direct Peel-off Technique", ACS Appl. Mater. Interfaces, vol. 7, Issue 10, 2015, pp. 5938-5943. cited by applicant

Choi et al., "Influence of removing PMMA residues on surface of CVD graphene using a contact-mode atomic force Microscope" RSC Adv., vol. 7, 2017, pp. 6943-6949. cited by applicant

CN101671112A English Translation Performed by USPTO Translations Service Center Apr. 2017. cited by applicant

Conradt, Reinhard, "I. Fragility and its Relation to Other Glass Properties," IMI-NFG's MITT Course on Relaxation Processes in Glass Lecture 21, Apr. 6-8, 2010, 61 slides. cited by applicant

Primary Examiner: Orlando; Amber R

Assistant Examiner: Miller; Cameron K

Background/Summary

(1) This application is a continuation of U.S. application Ser. No. 16/767,191 filed May 27, 2020, which claims the benefit of priority under 35 U.S.C. § 371 of International Application No. PCT/US18/063404, filed on Nov. 30, 2018, which claims the benefit of priority under 35 U.S.C. § 120 of U.S. Application Ser. No. 62/592,683 filed on Nov. 30, 2017, the content of which is relied upon and incorporated herein by reference in its entirety.

FIELD OF DISCLOSURE

(1) The disclosure relates to fusion formable glasses with high coefficients of thermal expansion and low fracture toughness designed for thermal tempering. The glasses are ideally suited to produce a "dicing" pattern when thermally tempered, even at very thin thicknesses. They have high thermal expansions at low and high temperatures to produce increased temper stresses once quenched, coupled with low fracture toughness which promotes crack bifurcation and enhanced fragility.

BACKGROUND

(2) Thermally-tempered glass, sometimes called safety glass, is often applied in situations where safe fracture behavior is required to prevent injury in the case of failure. For example, safety glass is used to strengthen automobile side and rear windows, as well as objects such as shower doors. The property of tempered glass that makes it so desirable in safety applications is that when it breaks, it shatters into rock salt-like, cubicle pieces which do not have sharp edges or needle-like points. This desired fracture behavior is called "dicing" and occurs when the glass has achieved full temper.

(3) In addition to the safety aspect of thermally tempered glass, tempering strengthens the glass, making it more damage resistant and durable. Because of the increased durability, tempered glass can be used in applications where normal glass would quickly break—for example, automotive windows, where the glass may be impacted by rocks or other hard materials. Due to the increase in

glass use in architectural, automotive, and electronic device applications, there is a continuing demand for thin, thermally strengthened glasses that are durable, but when broken, break in a 'safe' or dicing break pattern. However, as glass becomes thinner it becomes harder to produce any thermal tempering stresses at all, and the central tension required for a safe "dicing" fracture pattern increases—producing a compound challenge. The present disclosure solves this unmet need by disclosing glasses that produce enhanced temper stresses while needing to reach a lower stress level for dicing to occur.

SUMMARY

(4) In an aspect (1), the disclosure provides a glass composition comprising greater than 70 mol % SiO₂, greater than 0 to 20 mol % Al₂O₃, greater than 0 to 20 mol % of at least one alkaline earth oxide from the group consisting of MgO, CaO, BaO, or SrO, 3-16 mol % K₂O, >0-10 mol % B₂O₃. In an aspect (2), the disclosure provides the glass composition of aspect (1), comprising 72-90 mol % SiO₂. In an aspect (3), the disclosure provides the glass composition of aspect (1) or aspect (2), further comprising 0-16 mol % Na₂O and 3-22 mol % Na₂O+K₂O. In an aspect (4), the disclosure provides the glass composition of any of aspect (1)-(3), wherein the low temperature coefficient of thermal expansion from 25-300° C. is greater than 75×10⁻⁷ ppm/° C. In an aspect (5), the disclosure provides the glass composition of any of aspect (1)-(4), wherein the high temperature coefficient of thermal expansion is greater than 250×10⁻⁷ ppm/° C. In an aspect (6), the disclosure provides the glass composition of any of aspect (1)-(5), wherein the fracture toughness, K_{IC} is less than 0.65 MPa-m^{1/2}. In an aspect (7), the disclosure provides the glass composition of any of aspect (1)-(6), wherein the glass has a viscosity of 200 kP at a temperature of from 1000-1200° C. In an aspect (8), the disclosure provides the glass composition of any of aspect (1)-(7), wherein the glass has a viscosity of 35 kP at a temperature of from 1100-1300° C. In an aspect (9), the disclosure provides the glass composition of any of aspect (1)-(8), comprising 0.5 to 8 mol % or 1 to 5 mol % B₂O₃. In an aspect (10), the disclosure provides the glass composition of any of aspect (1)-(9), comprising >0-10 mol % or 3 to 10 mol % Al₂O₃. In an aspect (11), the disclosure provides the glass composition of any of aspect (1)-(10), comprising 2 to 20 mol % or 2 to 15 mol % MO. In an aspect (12), the disclosure provides the glass composition of any of aspect (1)-(11), comprising 8-16 mol % Na₂O+K₂O. In an aspect (13), the disclosure provides the glass composition of any of aspect (1)-(12), comprising 5-15 mol % K₂O. In an aspect (14), the disclosure provides the glass composition of any of aspects (1)-(13), wherein the glass is thermally tempered and has a depth of compression of at least about 10 microns. In an aspect (15), the disclosure provides the glass composition of any of aspects (1)-(14), wherein the glass is thermally tempered and has a surface compressive stress of at least 250 MPa. In an aspect (16), the disclosure provides the glass composition of any of aspects (1)-(15), wherein the glass meets the dicing standard ASTM C1048. (5) In an aspect (17), the disclosure provides a method of making the glass composition of any of aspects (1)-(16), the method comprising mixing SiO₂, Al₂O₃, at least one alkaline earth oxide from the group consisting of MgO, CaO, BaO, or SrO, K₂O; and B₂O₃ to create a homogenous melt. In an aspect (18), the disclosure provides the method of aspect (17), wherein the melt is formed into glass sheets and the glass sheets are subsequently thermally tempered. In an aspect (19), the disclosure provides the method of aspect (17) or aspect (18), wherein the glass composition is meets the dicing standard ASTM C1048. In an aspect (20), the disclosure provides the method of any of aspects (17)-(19), wherein the glass is melted and maintained at temperatures ranging from 1100-1650° C. for times ranging from about 6-16 hours, and annealed at about 500-650° C., where the glass is held at temperature for about 1 hour and subsequently cooled for at least 6 hours.

Description

DETAILED DESCRIPTION

(1) In the following description, whenever a group is described as comprising at least one of a group of elements and combinations thereof, it is understood that the group may comprise, consist essentially of, or consist of any number of those elements recited, either individually or in combination with each other. Similarly, whenever a group is described as consisting of at least one of a group of elements or combinations thereof, it is understood that the group may consist of any number of those elements recited, either individually or in combination with each other. Unless otherwise specified, a range of values, when recited, includes both the upper and lower limits of the range as well as any ranges therebetween. As used herein, the indefinite articles “a,” “an,” and the corresponding definite article “the” mean “at least one” or “one or more,” unless otherwise specified. It also is understood that the various features disclosed in the specification and the drawings can be used in any and all combinations.

(2) Where a range of numerical values is recited herein, comprising upper and lower values, unless otherwise stated in specific circumstances, the range is intended to include the endpoints thereof, and all integers and fractions within the range. It is not intended that the scope of the claims be limited to the specific values recited when defining a range. Further, when an amount, concentration, or other value or parameter is given as a range, one or more preferred ranges or a list of upper preferable values and lower preferable values, this is to be understood as specifically disclosing all ranges formed from any pair of any upper range limit or preferred value and any lower range limit or preferred value, regardless of whether such pairs are separately disclosed. Finally, when the term “about” is used in describing a value or an end-point of a range, the disclosure should be understood to include the specific value or end-point referred to. When a numerical value or end-point of a range does not recite “about,” the numerical value or end-point of a range is intended to include two embodiments: one modified by “about,” and one not modified by “about.”

(3) As used herein, the term “about” means that amounts, sizes, formulations, parameters, and other quantities and characteristics are not and need not be exact, but may be approximate and/or larger or smaller, as desired, reflecting tolerances, conversion factors, rounding off, measurement error and the like, and other factors known to those of skill in the art. It is noted that the terms “substantially” may be utilized herein to represent the inherent degree of uncertainty that may be attributed to any quantitative comparison, value, measurement, or other representation. These terms are also utilized herein to represent the degree by which a quantitative representation may vary from a stated reference without resulting in a change in the basic function of the subject matter at issue. Thus, a glass that is “free of Al.sub.2O.sub.3” is one in which Al.sub.2O.sub.3 is not actively added or batched into the glass, but may be present in very small amounts as a contaminant (e.g., 500, 400, 300, 200, or 100 parts per million (ppm) or less or).

(4) Unless otherwise specified, all compositions are expressed in terms of mole percent (mol %). Coefficients of thermal expansion (CTE) are expressed in terms of 10.sup.-7/° C., unless otherwise specified. The low temperature CTE (LTCTE) is measured over a temperature range from 25° C. to 300° C. and expressed in terms of 10.sup.-7/° C. The high temperature CTE (HTCTE) is measured at the temperature above glass transition region and expressed in terms of 10.sup.-7/° C. The sum of the LTCTE and the HTCTE is expressed in terms of 10.sup.-7/° C. The density in terms of grams/cm.sup.3 was measured via the Archimedes method (ASTM C693). Young's modulus, shear modulus, and Poisson's Ratio were measured via the ASTM C623 standard.

Glass Compositions

(5) In thermal tempering, a glass product is heated to near the softening temperature and then rapidly quenched, for example, by blowing cold air on the surfaces. As a result, the glass will possess a lower surface temperature than the interior during cooling. As the center of the glass cools more slowly to room temperature it contracts to a smaller specific volume while the high

specific volume of the surface layer remains unchanged. This leads to a surface compressive layer that gives tempered glass its strength. The difference in specific volume is due to a combination of differences in the thermal expansion of the glass upon cooling and from a fictive temperature difference between the surface and the bulk. To a first approximation, the stress distribution in thermally tempered glass can be represented by a simple parabola, with the magnitude of the surface compressive stress approximately equal to twice the center tension.

(6) When thermally tempered glass breaks, unlike annealed glass, it shatters into rock-salt like pieces which do not have sharp edges or needle-like shapes. This behavior is particularly useful for situations where safe fracture behavior is necessary and it is for this reason that characterizing the fracture behavior of thermally tempered glass is of paramount importance. The desired fracture behavior is called “dicing” and occurs when the glass has achieved full temper. The dicing threshold of tempered glass is a somewhat arbitrarily defined fracture behavior which can be considered “safe” to the user in the event of glass failure. Standards for dicing thresholds exist worldwide, such as ASTM C1048 and ANSI Z97.1 in the United States, EN12150-1 in Europe, GOST 5727-88 in Russia, JIS R 3206 in Japan, and GB 15763.2 in China (all of which are hereby incorporated by reference). The standards across countries are similar in that they generally state a fragmented piece of tempered soda-lime glass is required to contain at least 30-40 fragments in an area of 50 mm×50 mm (1.6 fragments/cm²) for thick glasses (>3 mm), while Japanese standards in particular require at least 60 fragments in the case of thinner glass.

(7) The glasses disclosed herein have high coefficients of thermal expansion and can be used with a thermal tempering process to obtain improved fracture behavior when compared to commercially available thin glasses. The glasses described herein are needed to satisfy a growing demand for stronger but thinner thermally strengthened glasses for commercial electronics, automotive and architectural applications where durability and/or scratch resistance are desired along with a “safe” break pattern. Additionally, the glasses must also retain a significant chemical durability, as they will likely be exposed to the elements for extended periods of time.

(8) It has been found herein that in order for thin glasses (3 mm or less, 2 mm or less, or 1 mm or less) to be thermally temperable and retain the desired fracture pattern, the low temperature coefficient of thermal expansion (LTCTE) should be $75 \times 10^{-7}/^{\circ}\text{C}$. or greater and the high temperature coefficient of thermal expansion (HTCTE) should be $250 \times 10^{-7}/^{\circ}\text{C}$. or greater. In some embodiments, it has been found that in addition to the LTCTE and the HTCTE limitations, the glass must also have a fracture toughness (K_{IC}) is less than 0.65 MPa·m^{1/2}.

(9) In some embodiments, the glass comprises a combination of SiO₂, K₂O, Al₂O₃, B₂O₃, and alkaline earth oxides. For example, embodiments may comprise greater than 70 mol % SiO₂, greater than 0 mol % Al₂O₃, greater than 0 mol % B₂O₃, greater than 3 mol % K₂O, and greater than 0 mol % MO, where M is Ca, Ba, Sr, or Mg. In some embodiments, the glass may comprise greater than 72 mol % SiO₂, >0 to 10 mol % Al₂O₃, 0.5 to 5 mol % B₂O₃, 3 to 20 mol % K₂O, and 2 to 20 mol % MO, where M is Ca, Ba, Sr, or Mg. In other embodiments, the glass may comprise 72 to 90 mol % SiO₂, 3 to 10 mol % Al₂O₃, 1 to 5 mol % B₂O₃, 8 to 18 mol % K₂O, and 2 to 15 mol % MO, where M is Ca, Ba, Sr, or Mg.

(10) SiO₂, which is the largest oxide component of the embodied glasses, maybe included to provide high temperature stability and chemical durability. In some embodiments, the glass can comprise 70 mol % or greater SiO₂. In some embodiments, the glass can comprise 72 mol % or greater SiO₂. In some embodiments, the glass can comprise 72 to 90 mol % SiO₂. In some embodiments, the glass can comprise from 75 to 90 mol % SiO₂. In some embodiments, the glass can comprise 70 to 92 mol %, 70 to 90 mol %, 70 to 85 mol %, 70 to 80 mol %, 72 to 92 mol %, 72 to 90 mol %, 72 to 85 mol %, 72 to 80 mol %, 75 to 92 mol %, 75 to 90 mol %, 75 to 85 mol %, or 75 to 80 mol % SiO₂. In some embodiments, the glass comprises 70, 71, 72, 73, 74, 75, 76, 77, 78, 79, 80, 81, 82, 83, 84, 85, 86, 87, 88, 89, 90, 91 or 92 mol % SiO₂.

(11) Al.sub.2O.sub.3 may influence the structure of the glass and, additionally, lower the liquidus temperature and coefficient of thermal expansion, or enhance the strain point. In some embodiments, the glass can comprise greater than 0 mol % Al.sub.2O.sub.3. In some embodiments, the glass can comprise from >0 to 20 mol % Al.sub.2O.sub.3. In some embodiments, the glass can comprise from >0 to 10 mol %, 3 to 10 mol %, or 5 to 10 mol % Al.sub.2O.sub.3. In some embodiments, the glass can comprise from >0 to 20 mol %, >0 to 18 mol %, >0 to 15 mol %, >0 to 12 mol %, >0 to 10 mol %, >0 to 8 mol %, 1 to 20 mol %, 1 to 18 mol %, 1 to 15 mol %, 1 to 12 mol %, 1 to 10 mol %, 1 to 8 mol %, 3 to 20 mol %, 3 to 18 mol %, 3 to 15 mol %, 3 to 12 mol %, 3 to 10 mol %, 3 to 8 mol %, 5 to 20 mol %, 5 to 18 mol %, 5 to 15 mol %, 5 to 12 mol %, 5 to 10 mol %, 5 to 8 mol %, 7 to 20 mol %, 7 to 18 mol %, 7 to 15 mol %, 7 to 12 mol %, or 7 to 10 mol % Al.sub.2O.sub.3. In some embodiments, the glass can comprise about >0, 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, or 20 mol % Al.sub.2O.sub.3.

(12) Without being bound by theory, it is believed that incorporating B.sub.2O.sub.3 into the glasses described herein impacts the coefficient of thermal expansion, especially at high temperatures, and improves the temperability of the glasses. In some embodiments, when present, the glass can comprise >0 mol % to 10 mol % B.sub.2O.sub.3. In some embodiments, the glass can comprise from 0.5 to 10 mol %, 0.5 mol % to 8 mol % or from 1 mol % to 6 mol %

B.sub.2O.sub.3. In some embodiments, the glass can comprise from 1 to 5 mol % B.sub.2O.sub.3. In some embodiments, the glass can comprise from >0 to 10 mol %, >0 to 8 mol %, >0 to 6 mol %, >0 to 5 mol %, >0 to 4 mol %, 0.5 to 10 mol %, 0.5 to 8 mol %, 0.5 to 6 mol %, 0.5 to 5 mol %, 0.5 to 4 mol %, 1 to 10 mol %, 1 to 8 mol %, 1 to 6 mol %, 1 to 5 mol %, 1 to 4 mol %, 2 to 10 mol %, 2 to 8 mol %, 2 to 6 mol %, 2 to 5 mol %, or 2 to 4 mol %. In some embodiments, the glass can comprise about 0, >0, 0.5, 1, 1.5, 2, 3, 4, 5, 6, 7, 8, 9, or 10 mol % B.sub.2O.sub.3.

(13) Alkaline earth oxides may improve desirable properties in the materials, including influencing the Young's modulus and the coefficient of thermal expansion. In some embodiments, the glass comprises from >0 mol % to about 20 mol % MO ($0 \text{ mol \%} < \text{MO} \leq 20 \text{ mol \%}$), where M is the sum of the alkaline earth metals Mg, Ca, Sr, and Ba, in the glass. In some embodiments, the glass can comprise from 2 to 20 mol % MO. In some embodiments, the glass can comprise from 2 to 15 mol % MO. In some embodiments, the glass can comprise about >0, 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, or 20 mol % MO.

(14) In some embodiments, the glasses comprise MgO, CaO, or SrO. In some embodiments, the glass can comprise greater than 0 mol % MgO. In some embodiments, the glass can comprise from >0 to 10 mol % MgO. In some embodiments, the glass can comprise from 3 to 10 mol %, 5 to 10 mol %, 5 to 8 mol % MgO. In some embodiments, the glass can comprise from >0 to 10 mol %, >0 to 8 mol %, >0 to 6 mol %, >0 to 4 mol %, >0 to 2 mol %, 1 to 10 mol %, 1 to 8 mol %, 1 to 6 mol %, 1 to 4 mol %, 1 to 2 mol %, 3 to 8 mol %, 3 to 6 mol %, 3 to 10 mol %, 5 to 8 mol %, 5 to 10 mol %, 7 to 10 mol %, or 8 to 10 mol % MgO. In some embodiments, the glass can comprise about >0, 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10 mol % MgO.

(15) In some embodiments, the glass can comprise greater than 0 mol % CaO. In some embodiments, the glass can comprise from >0 to 15 mol % CaO. In some embodiments, the glass can comprise from >0 to 5 mol %, 6 to 13 mol %, 5 to 15 mol %, 7 to 13 mol %, 7 to 11 mol %, 8 to 12 mol % CaO. In some embodiments, the glass can comprise from >0 to 15 mol %, >0 to 13 mol %, >0 to 11 mol %, >0 to 9 mol %, >0 to 7 mol %, >0 to 5 mol %, 1 to 15 mol %, 1 to 13 mol %, 1 to 11 mol %, 1 to 9 mol %, 1 to 7 mol %, 1 to 5 mol %, 3 to 15 mol %, 3 to 13 mol %, 3 to 11 mol %, 3 to 9 mol %, 3 to 7 mol %, 3 to 5 mol %, 5 to 15 mol %, 5 to 13 mol %, 5 to 11 mol %, 5 to 9 mol %, 5 to 7 mol %, 7 to 15 mol %, 7 to 13 mol %, 7 to 11 mol %, 7 to 9 mol %, 9 to 15 mol %, 9 to 13 mol %, 9 to 11 mol %, 11 to 15 mol %, or 11 to 13 mol % CaO. In some embodiments, the glass can comprise about >0, 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, or 15 mol % CaO.

(16) SrO may be present in some embodiments and in such embodiments, the glass can comprise from 0 to 10 mol % SrO. In some embodiments, the glass can comprise from >0 to 10 mol % SrO.

In some embodiments, the glass can comprise from 3 to 10 mol %, 5 to 10 mol %, 5 to 8 mol % SrO. In some embodiments, the glass can comprise from >0 to 10 mol %, >0 to 8 mol %, >0 to 6 mol %, >0 to 4 mol %, >0 to 2 mol %, 1 to 10 mol %, 1 to 8 mol %, 1 to 6 mol %, 1 to 4 mol %, 1 to 2 mol %, 3 to 8 mol %, 3 to 6 mol %, 3 to 10 mol %, 5 to 8 mol %, 5 to 10 mol %, 7 to 10 mol %, or 8 to 10 mol % SrO. In some embodiments, the glass can comprise about >0, 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10 mol % SrO.

(17) BaO may be present in some embodiments and in such embodiments, the glass can comprise from 0 to 15 mol % BaO. In some embodiments, the glass can comprise from 0 to 10 mol %, >0 to 5 mol %, 6 to 13 mol %, 5 to 15 mol %, 7 to 13 mol %, 7 to 11 mol %, 8 to 12 mol % BaO. In some embodiments, the glass can comprise from >0 to 15 mol %, >0 to 13 mol %, >0 to 11 mol %, >0 to 9 mol %, >0 to 7 mol %, >0 to 5 mol %, 1 to 15 mol %, 1 to 13 mol %, 1 to 11 mol %, 1 to 9 mol %, 1 to 7 mol %, 1 to 5 mol %, 3 to 15 mol %, 3 to 13 mol %, 3 to 11 mol %, 3 to 9 mol %, 3 to 7 mol %, 3 to 5 mol %, 5 to 15 mol %, 5 to 13 mol %, 5 to 11 mol %, 5 to 9 mol %, 5 to 7 mol %, 7 to 15 mol %, 7 to 13 mol %, 7 to 11 mol %, 7 to 9 mol %, 9 to 15 mol %, 9 to 13 mol %, 9 to 11 mol %, 11 to 15 mol %, or 11 to 13 mol % BaO. In some embodiments, the glass can comprise about >0, 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, or 15 mol % BaO.

(18) Na.sub.2O and K.sub.2O may improve the temperability of the glass and influence the coefficient of thermal expansion, especially at low temperatures. In some embodiments, the glass can comprise from 0 to 10 mol % Na.sub.2O. In some embodiments, the glass can comprise >0 to 10 mol % Na.sub.2O. In some embodiments, the glass can comprise 0 to 8 mol % Na.sub.2O. In some embodiments, the glass can comprise 2 to 6 mol % Na.sub.2O. In some embodiments, the glass can comprise from 0 to 10 mol %, 0 to 8 mol %, 0 to 6 mol %, 0 to 4 mol %, 0 to 2 mol %, >0 to 10 mol %, >0 to 8 mol %, >0 to 6 mol %, >0 to 4 mol %, >0 to 2 mol %, 2 to 10 mol %, 2 to 8 mol %, 2 to 6 mol %, 2 to 4 mol %, 5 to 16 mol %, 5 to 10 mol %, 5 to 8 mol %, or 8 to 10 mol % Na.sub.2O. In some embodiments, the glass can comprise 0, >0, 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10 mol % Na.sub.2O.

(19) In some embodiments, the glass can comprise from 3 to 20 mol % K.sub.2O. In some embodiments, the glass can comprise 5 to 18 mol % K.sub.2O. In some embodiments, the glass can comprise 8 to 12 mol % K.sub.2O. In some embodiments, the glass can comprise from 3 to 20 mol %, 3 to 18 mol %, 3 to 15 mol %, 3 to 12 mol %, 3 to 10 mol %, 3 to 8 mol %, 5 to 20 mol %, 5 to 18 mol %, 5 to 15 mol %, 5 to 12 mol %, 5 to 10 mol %, 5 to 8 mol %, 8 to 20 mol %, 8 to 18 mol %, 8 to 15 mol %, 8 to 12 mol %, 8 to 10 mol %, 10 to 20 mol %, 10 to 18 mol %, 10 to 15 mol %, 10 to 12 mol %, 12 to 20 mol %, 12 to 18 mol %, or 12 to 15 mol % K.sub.2O. In some embodiments, the glass can comprise 0, >0, 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, or 20 mol % K.sub.2O.

(20) In some embodiments, Li.sub.2O may be present and in such embodiments, the glass can comprise from 0 to 5 mol % Li.sub.2O. In some embodiments, the glass can comprise from >0 to 5 mol % Li.sub.2O. In some embodiments, the glass can comprise from about >0 to 3.5 mol % Li.sub.2O or 0.2 to 3 mol % Li.sub.2O. In some embodiments, the glass can comprise from 1 to 4 mol % Li.sub.2O. In some embodiments, the glass can comprise from 0.2 to 5 mol %, 0.2 to 4 mol %, 0.2 to 3 mol %, 0.2 to 2 mol %, >0 to 5 mol %, >0 to 4 mol %, >0 to 3 mol %, >0 to 2 mol %, 1 to 5 mol %, 1 to 4 mol %, or 1 to 3 mol % Li.sub.2O. In some embodiments, the glass can comprise about 0, >0, 1, 2, 3, 4, or 5 mol % Li.sub.2O.

(21) In some embodiments, the total amount of the alkalis Na.sub.2O and K.sub.2O or Li.sub.2O, Na.sub.2O, and K.sub.2O is important to the glass properties. In some embodiments, the glass can comprise 3 to 22 mol % Na.sub.2O+K.sub.2O or Li.sub.2O+Na.sub.2O+K.sub.2O. In some embodiments, the glass can comprise 5 to 20 mol % Na.sub.2O+K.sub.2O or Li.sub.2O+Na.sub.2O+K.sub.2O. In some embodiments, the glass can comprise 5 to 15 mol % Na.sub.2O+K.sub.2O or Li.sub.2O+Na.sub.2O+K.sub.2O. In some embodiments, the glass can comprise 8 to 16 mol % Na.sub.2O+K.sub.2O or Li.sub.2O+Na.sub.2O+K.sub.2O. In some

embodiments, the glass can comprise 9 to 14 mol % Na.sub.2O+K.sub.2O or Li.sub.2O+Na.sub.2O+K.sub.2O. In some embodiments, the glass can comprise from 3 to 22 mol %, 5 to 22 mol %, 8 to 22 mol %, 3 to 20 mol %, 5 to 20 mol %, 8 to 20 mol %, 3 to 15 mol %, 5 to 15 mol %, 8 to 15 mol %, 3 to 12 mol %, 5 to 12 mol %, or 8 to 12 mol % Na.sub.2O+K.sub.2O or Li.sub.2O+Na.sub.2O+K.sub.2O. In some embodiments, the glass can comprise 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, or 22 mol % Na.sub.2O+K.sub.2O or Li.sub.2O+Na.sub.2O+K.sub.2O.

(22) Additional components can be incorporated into the glass to provide additional benefits or may be incorporated as contaminants typically found in commercially-prepared glass. For example, additional components can be added as coloring or fining agents (e.g., to facilitate removal of gaseous inclusions from melted batch materials used to produce the glass) and/or for other purposes. In some embodiments, the glass may comprise one or more compounds useful as ultraviolet radiation absorbers. In some embodiments, the glass can comprise 3 mol % or less ZnO, TiO.sub.2, CeO, MnO, Nb.sub.2O.sub.5, MoO.sub.3, Ta.sub.2O.sub.5, WO.sub.3, SnO.sub.2, Fe.sub.2O.sub.3, As.sub.2O.sub.3, Sb.sub.2O.sub.3, Cl, Br, or combinations thereof. In some embodiments, the glass can comprise from 0 to about 3 mol %, 0 to about 2 mol %, 0 to about 1 mol %, 0 to 0.5 mol %, 0 to 0.1 mol %, 0 to 0.05 mol %, or 0 to 0.01 mol % ZnO, TiO.sub.2, CeO, MnO, Nb.sub.2O.sub.5, MoO.sub.3, Ta.sub.2O.sub.5, WO.sub.3, SnO.sub.2, Fe.sub.2O.sub.3, As.sub.2O.sub.3, Sb.sub.2O.sub.3, Cl, Br, or combinations thereof. The glasses, according to some embodiments, can also include various contaminants associated with batch materials and/or introduced into the glass by the melting, fining, and/or forming equipment used to produce the glass. For example, in some embodiments, the glass can comprise from 0 to about 3 mol %, 0 to about 2 mol %, 0 to about 1 mol %, 0 to about 0.5 mol %, 0 to about 0.1 mol %, 0 to about 0.05 mol %, or 0 to about 0.01 mol % SnO.sub.2 or Fe.sub.2O.sub.3, or combinations thereof.

(23) Non-limiting examples of amounts of precursor oxides for forming the embodied glasses are listed in Table 1, along with the properties of the resulting glasses.

(24) TABLE-US-00001

TABLE 1	Analyzed mol % Glass A	Glass B	Glass C	Glass D	Glass E
SiO.sub.2	76.60	75.29	75.11	75.75	76.10
B.sub.2O.sub.3	1.88	2.35	2.57	2.15	2.41
Al.sub.2O.sub.3	6.32	7.06	7.00	6.07	6.03
K.sub.2O	11.61	12.32	11.41	11.08	11.11
CaO	0.00	0.00	0.00	0.00	0.00
SrO	3.84	2.93	3.86	4.89	3.87
P.sub.2O.sub.5	0.00	0.00	0.00	0.00	0.42
SnO.sub.2	0.05	0.05	0.05	0.05	0.05
LTCTE (ppm/° C.)	7.87	7.80	7.71	7.69	—
HTCTE (ppm/° C.)	—	27.31	28.54	27.12	—
K.sub.IC (MPa-m.sup.1/2)	0.55	—	0.65	0.62	—
Density (g/cm.sup.3)	2.471	2.456	2.471	2.492	—
Strain Pt (° C.)	600	607	610	611	—
Anneal Pt (° C.)	652	658	662	662	—
Softening Pt (° C.)	876	889	890	882	—
SOC (TPa.sup.-1)	2.965	3.121	3.049	3.015	—
Refractive Index	1.5005	1.5005	1.5019	1.5038	—
200 Poise	1720	1762	1758	1706	1762
temperature (° C.)	35000	1172	1190	1204	1181
200000 Poise	1072	1085	1099	1080	1107
temperature (° C.)	—	—	—	—	—
Analyzed mol % Glass F	Glass G	Glass H	Glass I	Glass J	
SiO.sub.2	75.64	76.00	75.83	75.35	75.35
B.sub.2O.sub.3	2.25	2.10	2.29	2.34	1.58
Al.sub.2O.sub.3	6.05	6.04	6.02	6.00	6.00
K.sub.2O	12.01	11.94	11.81	12.18	13.18
CaO	4.01	0.00	0.00	0.00	0.00
SrO	0.00	3.84	3.89	3.86	3.85
P.sub.2O.sub.5	0.00	0.04	0.11	0.22	0.00
SnO.sub.2	0.05	0.05	0.05	0.05	0.05
LTCTE (ppm/° C.)	7.82	7.85	7.78	7.91	8.33
HTCTE (ppm/° C.)	27.68	24.72	27.08	26.88	27.21
K.sub.IC (MPa-m.sup.1/2)	0.59	0.67	0.62	—	0.63
Density (g/cm.sup.3)	2.415	2.476	2.475	2.476	2.480
Strain Pt (° C.)	615	598	602	599	586
Anneal Pt (° C.)	667	649	654	649	638
Softening Pt (° C.)	887	872.2	870.8	875.3	858.3
SOC (TPa.sup.-1)	3.050	2.976	3.011	2.967	2.951
Refractive Index	1.5012	1.5029	1.5022	1.5018	1.5030
200 Poise	1721	1695	1715	1684	1684
temperature (° C.)	35000	1185	1162	1162	1157
200000 Poise	1084	1062	1063	1057	1049
temperature (° C.)	—	—	—	—	—

(25) As noted above, the embodied glasses of one or more embodiments may exhibit a color. In some embodiments, it is desirable for the glass to have a green-yellow to gold to amber color. In particular embodiments, these colors may be combined with the blue color of a crystalline silicon photovoltaic cell to create a dark blue to black color that is aesthetically pleasing. In some

embodiments, the glasses exhibit a color presented in SCE color space coordinates (determined from reflectance spectra measurements using a spectrophotometer, with illuminant D65 and specular reflectance excluded), with the following ranges: a^* =from about -10 to about 30; b^* =from about 0 to about 30; and $L^*>80$ for a glass having a thickness of 2.7 mm. In some embodiments, the glasses exhibit a color presented in SCI color space coordinates of a^* =from about -5 to about -1; b^* =from about 5 to about 18; and $L^*>83$ for a glass having a thickness of 2.7 mm. In some applications, the combination of the photovoltaic cell and the glass combine to produce a desired color. In such application, the SCE color space coordinates (determined from reflectance spectra measurements using a spectrophotometer, with illuminant D65 and specular reflectance excluded) of the combination of the glass and the photovoltaic cell may comprise the following ranges: a^* =from about 0 to about 10; b^* =from about -15 to about 0; and L^* from about 10 to about 50.

(26) In some embodiments, the glass can be strengthened via thermal or chemical tempering. In some embodiments, the glass can be strengthened to include compressive stress (CS) that extends from a surface thereof to a depth of compression (DOC). The compressive stress regions are balanced by a central portion exhibiting a tensile stress. At the DOC, the stress crosses from a positive (compressive) stress to a negative (tensile) stress. Such strengthening methods comprise both thermal tempering and chemical tempering.

(27) The glasses described herein are particularly capable of being thermally tempered. The process of thermal tempering is well known in the art. To thermally temper a glass article, the article is heated to near the softening temperature and then rapidly cooled or quenched. As a result, the glass will possess a lower surface temperature than the interior during cooling. The temperature difference is maintained until the surface of the glass cools to at least its strain point or lower, such as room temperature. Because the center of the glass cools more slowly, it contracts to a smaller specific volume while the high specific volume of the surface layer remains unchanged. This leads to a surface compressive layer that gives tempered glass its strength. The difference in specific volume is, in part, due to differences in the thermal expansion of the glass upon cooling, while to a lesser extent from a fictive temperature difference between the surface and the bulk. To a first approximation, the stress distribution in thermally tempered glass can be represented by a simple parabola, with the magnitude of the surface compressive stress approximately equal to twice the center tension.

(28) As an alternative to thermal tempering, the glasses disclosed herein may be ion exchanged by immersion in at least one ion exchange bath containing molten salts (e.g., nitrates, sulfides, halides, or the like) of at least one alkali metal such as lithium, sodium, or potassium. Ion exchange is commonly used to chemically strengthen glasses. In one particular example, alkali cations within a source of such cations (e.g., a molten salt, or "ion exchange," bath) are exchanged with smaller alkali cations within the glass to achieve a layer under a compressive stress (CS) extending from the surface of the glass to a depth of compression (DOC) within the glass phase. For example, potassium ions from the cation source are often exchanged with sodium and/or lithium ions within the glass phase, and the $K^{sup.+}$ concentration profile correlates with the compressive stress and depth of layer. The ion exchange bath may contain a salt (or salts) of a single alkali metal (e.g., sulfides, nitrates, or halides of Li, Na, or K) or salts of two or more alkali metals (e.g., sulfides, nitrates, or halides of Li and Na, or sulfides, nitrates, or halides of Na and K). Ion exchange is carried out in the ion exchange bath at temperatures ranging from about 390° C. to about 550° C. for times ranging from about 0.5 hour to about 24 hours.

(29) The glass, in some embodiments, is ion exchanged and has a compressive layer extending from a surface to a depth of compression (DOC) of at least about 10 μm or, in some embodiments, at least about 30 μm into the glass, or in some embodiments up to about 10, 15, 20 or 25% into the glass as measured by thickness (surface to center). In some embodiments, the compressive layer extends from the surface of the glass to a depth of up to about 20% of the thickness of the glass. In

some embodiments, the glass may be strengthened to exhibit a surface compressive stress in a range from 250 MPa to 800 MPa or greater.

(30) In the strengthened glass, the depth of the compressive layer may be determined by electron microprobe, glow-discharge optical emission spectroscopy (GDOES, which is a technique for measuring depth profiles of constituent elements in a solid sample by detecting emissions from atoms accommodated in plasma by sputtering), or similar techniques that can provide composition data as a function of depth, where data would show incorporation of Na (where Na.sup.+ replaces Li.sup.+ in the glass phase) and/or K at the surfaces. The DOC of a precursor glass may be measured by surface stress meter (FSM) using commercially available instruments such as the FSM-6000, manufactured by Orihara Industrial Co., Ltd. (Japan). Surface stress measurements rely upon the accurate measurement of the stress optical coefficient (SOC), which is related to the birefringence of the glass. SOC in turn is measured by those methods that are known in the art, such as fiber and four point bend methods, both of which are described in ASTM standard C770-98 (2013), entitled “Standard Test Method for Measurement of Glass Stress-Optical Coefficient,” the contents of which are incorporated herein by reference in their entirety, and a bulk cylinder method. CS may also be measured by measured by FSM. As used herein CS may be the “maximum compressive stress” which is the highest compressive stress value measured within the compressive stress layer. In some embodiments, the maximum compressive stress is located at the surface of the glass. In other embodiments, the maximum compressive stress may occur at a depth below the surface, giving the compressive profile the appearance of a “buried peak.”

(31) The thermally or chemically strengthened glasses or articles disclosed herein may be incorporated into another article such as an article with a display (or display articles) (e.g., consumer electronics, including mobile phones, tablets, computers, navigation systems, and the like), architectural articles (e.g., windows, skylights, shingles), transportation articles (e.g., automotive, trains, aircraft, sea craft, etc.), appliance articles, or any article that would benefit from transparency, scratch-resistance, abrasion resistance or a combination thereof. In other embodiments, the glass forms a portion of a consumer electronic product, such as a cellular phone or smart phone, laptop computer, tablet, or the like. Such consumer electronic products typically comprise a housing having front, back, and side surfaces, and include electrical components such as a power source, a controller, a memory, a display, and the like, which are at least partially internal to the housing. In some embodiments, the glass described herein comprises at least a portion of a protective element, such as, but not limited to, the housing and/or display of a consumer electronic product.

Processes for Making Glasses

(32) Glasses having the oxide contents listed in Table 1 can be made via traditional methods. For example, in some embodiments, the precursor glasses can be formed by thoroughly mixing the requisite batch materials (for example, using a turbular mixer) in order to secure a homogeneous melt, and subsequently placing into silica and/or platinum crucibles. The crucibles can be placed into a furnace and the glass batch melted and maintained at temperatures ranging from 1250-1650° C. for times ranging from about 6-16 hours. The melts can thereafter be poured into steel molds to yield glass slabs. Subsequently, those slabs can be transferred immediately to an annealer operating at about 500-650° C., where the glass is held at temperature for about 1 hour and subsequently cooled overnight. In another non-limiting example, precursor glasses are prepared by dry blending the appropriate oxides and mineral sources for a time sufficient to thoroughly mix the ingredients. The glasses are melted in platinum crucibles at temperatures ranging from about 1100° C. to about 1650° C. and held at temperature for about 16 hours. The resulting glass melts are then poured onto a steel table to cool. The precursor glasses are then annealed at appropriate temperatures.

(33) Tempering of the embodied glasses was achieved using conventional processes wherein the glasses were heated in a radiant energy furnace or a convection furnace (or a “combined mode” furnace using both techniques) to a predetermined temperature, then gas cooling (“quenching”),

typically via convection by blowing large amounts of ambient air against or along the glass surface. (34) While typical embodiments have been set forth for the purpose of illustration, the foregoing description should not be deemed to be a limitation on the scope of the disclosure or appended claims. Accordingly, various modifications, adaptations, and alternatives may occur to one skilled in the art without departing from the spirit and scope of the present disclosure or appended claims.

Claims

1. A method of making a glass article, comprising: mixing and melting batch constituents comprising: from 75 to 90 mol % SiO_2 ; from 7 to 20 mol % Al_2O_3 ; greater than 0 to 20 mol % of at least one alkaline earth oxide selected from the group consisting of MgO , CaO , BaO , or SrO ; from 8 to 20 mol % K_2O ; greater than 0 to 10 mol % B_2O_3 , and 0 mol % Na_2O to form a melt of the glass, wherein a low temperature coefficient of thermal expansion from 25° C. to 300° C. of the glass is greater than $75 \times 10^{-7} \text{ ppm/}^\circ \text{C}$., and wherein a fracture toughness, K_{IC} of the glass is less than 0.65 MPa $\cdot\text{m}^{1/2}$.
2. The method of claim 1, further comprising forming the melt into glass sheets.
3. The method of claim 2, further comprising thermally tempering the glass sheets.
4. The method of claim 3, further comprising maintaining the melt at temperatures ranging from 1100-1650° C. for times ranging from about 6-16 hours, wherein the glass sheets meet dicing standard ASTM C1048 after the thermal tempering.
5. The method of claim 4, further comprising annealing the glass sheets at about 500-650° C.
6. The method of claim 5, wherein during the annealing the glass is held at temperature for about 1 hour and subsequently cooled for at least 6 hours.
7. The method of claim 1, wherein a high temperature coefficient of thermal expansion of the glass is greater than $250 \times 10^{-7} \text{ ppm/}^\circ \text{C}$.
8. The method of claim 1, wherein the glass has a viscosity of 200 kP at a temperature within a range of 1000-1200° C.
9. The method of claim 1, wherein the glass has a viscosity of 35 kP at a temperature within a range of 1100-1300° C.
10. The method of claim 1, wherein the mixing comprises mixing from 0.5 to 8 mol % B_2O_3 .
11. The method of claim 1, wherein the mixing comprises mixing from 2 to 20 mol % MgO .
12. The method of claim 1, wherein the mixing comprises mixing from 11 to 20 mol % K_2O .
13. The method of claim 1, wherein the glass has a surface compressive stress of at least 250 MPa.
14. The method of claim 1, wherein the glass meets the dicing standard ASTM C1048.
15. The method of claim 3, wherein the glass has a depth of compression of at least about 10 microns, and the depth of compression extends up to about 25% into the glass as measured by thickness from surface to a center of the glass.
16. The method of claim 1, wherein the mixing comprises mixing: from 7 to 17 mol % Al_2O_3 ; from 0 to 10 mol % of the at least one alkaline earth oxide; and from 8 to 18 mol % K_2O .
17. The method of claim 1, wherein the mixing comprises mixing 0 mol % CaO .
18. A method of making a glass article, comprising: mixing and melting batch constituents comprising: from 75 to 90 mol % SiO_2 ; from 7 to 20 mol % Al_2O_3 ; greater than 0 to 20 mol % of at least one alkaline earth oxide selected from the group consisting of MgO , CaO , BaO , or SrO ; from 8 to 20 mol % K_2O ; and greater than 0 to 2.57 mol % B_2O_3 to form a melt of the glass, wherein the glass exhibits a 200 Poise temperature that is within a range of from 1684° C. to 1762° C.
19. The method of claim 1, wherein the mixing comprises mixing from greater than 0 to 2.57 mol % B_2O_3 .

20. The method of claim 18, wherein the mixing comprises mixing from 12 to 20 mol % K.sub.2O, and the glass exhibits a 200 Poise temperature that is within a range of 1700° C. to 1762° C.
