

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent

12411404

Kind Code

B2

Date of Patent

September 09, 2025

Inventor(s)

Tien; Chun-Chieh et al.

Method of manufacturing phase shift photo masks

Abstract

In a method of manufacturing a photo mask, a resist layer is formed over a mask blank, which includes a mask substrate, a phase shift layer disposed on the mask substrate and a light blocking layer disposed on the phase shift layer. A resist pattern is formed by using a lithographic operation. The light blocking layer is patterned by using the resist pattern as an etching mask. The phase shift layer is patterned by using the patterned light blocking layer as an etching mask. A border region of the mask substrate is covered with an etching hard cover, while a pattern region of the mask substrate is opened. The patterned light blocking layer in the pattern region is patterned through the opening of the etching hard cover. A photo-etching operation is performed on the pattern region to remove residues of the light blocking layer.

Inventors: Tien; Chun-Chieh (Kaohsiung, TW), Chiang; Cheng-Hsuen (Miaoli, TW), Chen; Chih-Ming (Dasi Township, TW), Lin; Cheng-Ming (Siluo Township, TW), Huang; Yen-Wei (Tainan, TW), Chang; Hao-Ming (Pingtung, TW), Lin; Kuo-Chin (Tainan, TW), Lee; Kuan-Shien (Taichung, TW)

Applicant: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Family ID: 66432193

Assignee: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.
(Hsinchu, TW)

Appl. No.: 18/411091

Filed: January 12, 2024

Prior Publication Data

Document Identifier

Publication Date

US 20240184195 A1

Jun. 06, 2024

Related U.S. Application Data

continuation parent-doc US 15905543 20180226 US 10739671 20200811 child-doc US 16989744
division parent-doc US 16989744 20200810 US 11906898 child-doc US 18411091
us-provisional-application US 62584556 20171110

Publication Classification

Int. Cl.: **G03F1/32** (20120101); **G03F1/38** (20120101); **G03F1/80** (20120101); **H01L21/308** (20060101)

U.S. Cl.:

CPC **G03F1/32** (20130101); **G03F1/38** (20130101); **G03F1/80** (20130101); **H01L21/3083** (20130101);

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5101420	12/1991	Kushibiki	430/5	G03F 7/70858
5437757	12/1994	Rice et al.	N/A	N/A
5641592	12/1996	Kim	N/A	N/A
5789117	12/1997	Chen	N/A	N/A
6123864	12/1999	Tam et al.	N/A	N/A
6607634	12/2002	Ye et al.	N/A	N/A
6803158	12/2003	Gordon et al.	N/A	N/A
7655364	12/2009	Kominato et al.	N/A	N/A
10276426	12/2018	Tu et al.	N/A	N/A
2002/0039689	12/2001	Yusa et al.	N/A	N/A
2002/0127821	12/2001	Ohya et al.	N/A	N/A
2003/0013023	12/2002	Chan	430/5	G03F 1/80
2005/0150860	12/2004	Fujisawa	N/A	N/A
2007/0012336	12/2006	Su et al.	N/A	N/A
2007/0190459	12/2006	Hashimoto et al.	N/A	N/A
2008/0199783	12/2007	Chang et al.	N/A	N/A
2009/0075181	12/2008	Ha	N/A	N/A
2009/0246645	12/2008	Nozawa	430/5	G03F 1/34
2009/0253054	12/2008	Kominato et al.	N/A	N/A
2010/0248493	12/2009	Watanabe	438/735	G03F 1/54
2011/0086296	12/2010	Moon	430/5	G03F 1/32
2011/0159411	12/2010	Olson et al.	N/A	N/A
2014/0224427	12/2013	Takahashi	156/345.51	H01J 37/32715
2014/0329171	12/2013	Imaizumi et al.	N/A	N/A

2016/0167167	12/2015	McCallum et al.	N/A	N/A
2017/0275759	12/2016	Kurita et al.	N/A	N/A
2018/0259843	12/2017	Fukaya et al.	N/A	N/A
2018/0284603	12/2017	Iino et al.	N/A	N/A
2018/0335691	12/2017	Nam	N/A	G03F 1/26
2019/0252237	12/2018	Tu et al.	N/A	N/A
2020/0371425	12/2019	Tien et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
202600360	12/2011	CN	N/A
S6090452	12/1984	JP	N/A
H04-094125	12/1991	JP	N/A
H04-303928	12/1991	JP	N/A
2004306134	12/2003	JP	C03C 23/0025
2012074533	12/2011	JP	N/A
2014154866	12/2013	JP	N/A
2014204062	12/2013	JP	N/A
480623	12/2001	TW	N/A

OTHER PUBLICATIONS

Non-Final Office Action issued in U.S. Appl. No. 15/905,543, dated Sep. 26, 2019. cited by applicant

Final Office Action issued in U.S. Appl. No. 15/905,543, dated Jan. 16, 2020. cited by applicant

Notice of Allowance issued in U.S. Appl. No. 15/905,543, dated Apr. 2, 2020. cited by applicant

Non-Final Office Action issued in U.S. Appl. No. 16/989,744, dated Apr. 19, 2023. cited by applicant

Notice of Allowance issued in U.S. Appl. No. 16/989,744, dated Oct. 13, 2023. cited by applicant

Primary Examiner: Angebranndt; Martin J

Attorney, Agent or Firm: STUDEBAKER BRACKETT PLLC

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a divisional application of U.S. non-provisional application Ser. No. 16/989,744, filed Aug. 10, 2020, which claims priority to U.S. non-provisional application Ser. No. 15/905,543 (now U.S. Pat. No. 10,739,671) filed Feb. 26, 2018, which claims priority to U.S. Provisional Patent Application 62/584,556, filed Nov. 10, 2017, the entire disclosures of which are incorporated herein by reference.

TECHNICAL FIELD

(1) The disclosure relates to methods of manufacturing phase shift photo masks.

BACKGROUND

(2) As semiconductor device feature sizes have decreased to sizes smaller than the wavelength of light used in photolithographic processes, the diffraction of light at feature pattern edges formed on the reticle causes a loss of resolution in transferring the reticle pattern to the wafer photoresist. To

increase the resolution of photolithographic pattern transfer, phase shift masks have been developed where the phase of the wavefronts of light passing through alternating portions of the reticle pattern are shifted out of phase with respect to light passing through adjacent portions to produce destructively interfering wavefronts to reduce undesired exposure of the wafer photoresist due to diffraction of light at feature edges of the reticle pattern. As a result, the contrast, and therefore transferable resolution of the reticle pattern is improved.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) The present disclosure is best understood from the following detailed description when read with the accompanying figures. It is emphasized that, in accordance with the standard practice in the industry, various features are not drawn to scale and are used for illustration purposes only. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.
- (2) FIG. 1 shows a view of a phase shift photo mask.
- (3) FIG. 2 shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to one embodiment of the present disclosure.
- (4) FIG. 3 shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to one embodiment of the present disclosure.
- (5) FIG. 4 shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to one embodiment of the present disclosure.
- (6) FIG. 5 shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to one embodiment of the present disclosure.
- (7) FIG. 6 shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to one embodiment of the present disclosure.
- (8) FIG. 7 shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to one embodiment of the present disclosure.
- (9) FIG. 8 shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to one embodiment of the present disclosure.
- (10) FIG. 9 shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to one embodiment of the present disclosure.
- (11) FIG. 10 shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to one embodiment of the present disclosure.
- (12) FIG. 11 shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to one embodiment of the present disclosure.
- (13) FIG. 12 shows a schematic view of a hard etching cover according to one embodiment of the present disclosure.
- (14) FIG. 13A shows a schematic cross sectional view of a side frame shape of the hard etching cover according to one embodiment of the present disclosure.
- (15) FIG. 13B shows a schematic cross sectional view of a side frame shape of the hard etching cover according to another embodiment of the present disclosure.
- (16) FIG. 13C shows a schematic cross sectional view of a side frame shape of the hard etching cover according to another embodiment of the present disclosure.
- (17) FIG. 13D shows a schematic cross sectional view of a side frame shape of the hard etching cover according to another embodiment of the present disclosure.
- (18) FIG. 14 shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to another embodiment of the present disclosure.
- (19) FIG. 15 shows one of various stages of a sequential manufacturing process of a phase shift

photo mask according to another embodiment of the present disclosure.

(20) FIG. **16** shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to another embodiment of the present disclosure.

(21) FIG. **17** shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to another embodiment of the present disclosure.

(22) FIG. **18** shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to another embodiment of the present disclosure.

(23) FIG. **19** shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to another embodiment of the present disclosure.

(24) FIG. **20** shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to another embodiment of the present disclosure.

(25) FIG. **21** shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to another embodiment of the present disclosure.

(26) FIG. **22** shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to another embodiment of the present disclosure.

(27) FIG. **23** shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to another embodiment of the present disclosure.

(28) FIG. **24** shows one of various stages of a sequential manufacturing process of a phase shift photo mask according to another embodiment of the present disclosure.

DETAILED DESCRIPTION

(29) It is to be understood that the following disclosure provides many different embodiments, or examples, for implementing different features of the invention. Specific embodiments or examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, dimensions of elements are not limited to the disclosed range or values, but may depend upon process conditions and/or desired properties of the device. Moreover, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed interposing the first and second features, such that the first and second features may not be in direct contact. Various features may be arbitrarily drawn in different scales for simplicity and clarity.

(30) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The device may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly. In addition, the term “made of” may mean either “comprising” or “consisting of.” In the present disclosure, a phrase “one of A, B and C” means “A, B and/or C” (A, B, C, A and B, A and C, B and C, or A, B and C), and does not mean one element from A, one element from B and one element from C, unless otherwise described.

(31) Embodiments of the present disclosure provide a method of manufacturing a phase shift photo mask with lower chromium (Cr) defect density.

(32) While there exists within the art of microelectronic fabrication various types of phase shift photo masks which effectively provide for enhanced intensity resolution of a photo exposure radiation beam passed through a phase shift photo mask for use, when forming a patterned photoresist layer from a blanket photoresist layer, from a practical perspective of ease of fabrication, a particularly desirable phase shift photo mask is an attenuated phase shift photo mask.

(33) FIG. **1** shows a plan view of an attenuated phase shift photo mask and FIGS. **11** and **24** show cross sectional views of the attenuated phase shift photo mask.

(34) A phase shift photo mask as shown in FIG. 1 includes a pattern region PR, in which various circuit patterns are fabricated with a phase shift layer, and an opaque border region BR surrounding the pattern region PR. As shown in FIGS. 11 and 24, an attenuated phase shift photo mask includes a transparent substrate 10 having formed thereupon a series of patterned semi-transparent phase shift layers 15 disposed in the pattern region PR. Within the attenuated phase shift photo mask, the series of patterned semi-transparent phase shift layers is formed of a semi-transparent masking material, typically and preferably having a transmissivity of from about 3 percent to about 8 percent of an incident photo exposure radiation beam incident upon the phase shift photo mask. The incident photo exposure radiation beam (e.g., deep ultra violet light) includes a first incident light which passes through only the transparent substrate 10, a second incident light which passes through both the transparent substrate 10 and the patterned semi-transparent phase shift layer 15. The patterned semi-transparent phase shift layer 15 is formed of a composition, and in particular of a thickness, such that subsequent to passing through the attenuated phase shift photo mask, the first incident light and the second incident light are about 180 degrees out of phase, which in turn provides the enhanced intensity resolution of the exposure light once passed through the attenuated phase shift photo mask.

(35) The opaque border region BR is a light blocking region having a Cr containing layer. In some embodiments, the opaque border region BR may include patterns, which are formed by a Cr containing layer and a transparent region and includes a photo mask alignment mark, a photo mask number, a name of the photo mask, etc.

(36) As shown in FIGS. 11 and 24, the pattern area PR generally includes only the patterned semi-transparent phase shift layers, the border region BR includes light blocking patterns formed by, for example, metallic reflective material, such as a chromium layer. Accordingly, in a fabrication operations of the attenuated phase shift photo mask require etching of the light blocking layer and the phase shift layer.

(37) In the pattern region PR, the light blocking layer (e.g., Cr containing layer) is removed during a manufacturing operation of the phase shift photo mask. The Cr containing layer is removed, for example, by one or more photolithography and etching operations including plasm dry etching. In the present disclosure, an operation including one or more photolithography and etching operations may be referred to as a photo-etching operation. The Cr containing layer, however, may not be completely removed, leaving behind Cr residues. The Cr residues can be detected by a photo mask inspection operation, and when unacceptable Cr residues (e.g., size and/or amount of Cr residues) are found, the phase shift photo mask will undergo one or more additional photolithography and etching operations (photo-etching operation). The additional Cr removal operation and inspection operation may be repeated until no Cr residue (or Cr defect) is found or the detected Cr residues are below the threshold size and/or amount. Additional Cr removal operation may increase the cost of manufacturing a phase photo mask and a turn-around time of the manufacturing process.

(38) In the present disclosure, a novel manufacturing operation for a phase shift photo mask including a novel etching operation to effectively remove a Cr containing layer from the pattern region is disclosed.

(39) FIGS. 2-11 show various stages for a sequential manufacturing process of a phase shift photo mask according to an embodiment of the present disclosure. It is understood that in the sequential manufacturing process, one or more additional operations can be provided before, during, and after the stages shown in the drawings, and some of the operations described below can be replaced or eliminated for additional embodiments of the method. The order of the operations/processes may be interchangeable.

(40) First, a mask blank 10 is provided. The mask blank or a mask substrate 10 is made of a material transparent to deep ultra violet light (e.g., 245 nm light emitted from a KrF excimer laser or 193 nm light emitted from an ArF excimer laser). In some embodiments, the mask substrate 10 is made of quartz. In certain embodiments, a quartz mask substrate according to the 6025 SEMI

standard is used for the mask substrate **10**.

(41) As shown in FIG. 2, a phase shift layer **15** is formed on the mask substrate **10** and a light blocking layer **20** is formed on the phase shift layer **15**. The phase shift layer may also be referred to as a light attenuating layer. The phase shift layer **15** has a material and sufficient thickness to pass from about 4% to about 40% of incident light with a phase shift of the transmitted light of about 180 degrees. In some embodiments, the phase shift layer **15** is made of, for example, but not limited to, at least one layer of MoSi, molybdenum silicon nitride (MoSi.sub.xN.sub.y) and molybdenum silicon oxynitride (MoSi.sub.xO.sub.yN.sub.z). In other embodiments, the phase shift layer **15** is made of a silicon nitride based material, such as silicon nitride, silicon oxynitride, silicon carbo-nitride and/or silicon carbo-oxide. In certain embodiments, the phase shift layer **15** is made chromium based material, such as chromium oxide, chromium oxynitride (CrO.sub.xN.sub.y) and chromium nitride (CrN.sub.x). The phase shift layer **15** can be a monolayer or include two or more layers. In some embodiments, the phase shift layer **15** has a thickness of from about 50 nm to about 150 nm, depending on the optical properties of the material and the thickness required to retard the phase of transmitted light about 180 degrees. The phase shift layer **15** can be formed by ion beam deposition (IBD), atomic layer deposition (ALD), chemical vapor deposition (CVD), or physical vapor deposition (PVD) (sputtering).

(42) The light blocking layer **20** is substantially opaque (non-transmitting) to incident light, for example, deep ultra violet light. In some embodiments, the light blocking layer **20** is a chromium containing layer, for example formed of at least one layer of Cr, chromium oxynitride (CrO.sub.xN.sub.y) and chromium nitride (CrN.sub.x), having a thickness of less than about 50 nm to about 200 nm. The light blocking layer **20** can be formed by a sputtering method or other suitable film forming method.

(43) As shown in FIG. 2, a first photo resist layer **30** is formed over the light blocking layer **20**. Before the first photo resist layer **30** is formed, the photo mask blank with the phase shift layer **15** and the light blocking layer **20** is subject to inspection. Then, the first photo resist layer **30** is exposed with an electron beam according to a layout design having desired circuit patterns. FIG. 3 shows a cross sectional view after the exposed first photo resist layer **30** is developed with a developing solution. In some embodiments, after the development of the photo resist layer first, a post baking operation is performed to harden the developed photo resist pattern **35**.

(44) Further, by using the photo resist pattern **35** as an etching mask, the light blocking layer (Cr containing layer) **20** is etched, to form a pattern **36**. The etching of the light blocking layer **20** can be performed by dry etching and/or wet etching in some embodiments. After the light blocking layer **20** is etched, the photo resist pattern **35** is removed by appropriate removal and cleaning operations, as shown in FIG. 5.

(45) Next, as shown in FIG. 6, by using the pattern **36** formed by the light blocking layer **20** as an etching mask, the phase shift layer **15** is etched, to form a phase shift pattern **37**. The etching of the phase shift layer **15** can be performed by dry etching and/or wet etching in some embodiments. After the etching, the mask substrate is removed from the etching chamber, and a cleaning operation is performed in some embodiments.

(46) Subsequently, an etching hard cover **100** is placed over the photo mask as shown in FIG. 7. The etching hard cover **100** is a separately prepared piece and placed on or over the photo mask. The etching hard cover **100** covers the opaque border region BR and has an opening over the pattern region PR. In some embodiments, the etching hard cover **100** is manually placed on the photo mask by an operator, and the photo mask with the etching hard cover **100** is loaded into an etching apparatus. In other embodiments, the etching hard cover **100** is movably disposed inside an etching apparatus and when the photo mask is loaded, the etching hard cover **100** is placed on the photo mask by mechanical operations.

(47) By using the etching hard cover **100** as an etching mask, the light blocking layer **20** in the pattern region PR is removed. As shown in FIG. 8, the etching hard cover **100** covers a part of the

pattern region PR in some embodiments. Thus, the light blocking layer **20** located under the etching hard cover **100** in the pattern region PR is not etched, forming residues **22**. After the light blocking layer **20** in the pattern region PR is etched, the etching hard cover **100** is removed (detached) and a cleaning operation is performed in some embodiments. The removed etching hard cover **100** is placed on a holder and reused for the next-processed photo mask.

(48) Subsequently, a second photo resist layer **40** is coated on the patterned photo mask, and a lithography operation using electron beam lithography or optical lithography and a resist development operation are performed. As shown in FIG. **9**, the second photo resist pattern **40** formed on the light blocking layer **20** remains at the opaque border region BR.

(49) Then, as shown in FIG. **10**, by using the second photo resist pattern **40** formed on the border region BR as an etching mask, the light blocking layer **22** (residues) remaining on the phase shift layer **15** at the pattern region PR is etched. The etching of the light blocking layer **22** can be performed by dry etching in some embodiments. Then, the second photo resist pattern **40** is removed by an appropriate resist removal operation, as shown in FIG. **11**. After the etching, a cleaning operation is performed in some embodiments.

(50) After the cleaning operation, an inspection operation is performed to detect residues of the light blocking layer (e.g., Cr residues). When unacceptable Cr residues (e.g., size and/or amount of Cr residues) are found, the phase shift photo mask will undergo one or more additional photolithography and etching operations (photo-etching operation) similar to the operations described in relation to FIGS. **9** and **10**. The additional Cr removal operation and the inspection operation may be repeated until no Cr residue (or Cr defect) is found or the detected Cr residues are below the threshold size and/or amount.

(51) In the foregoing embodiment, the light blocking layer **20** in the pattern region PR is first “roughly” etched and removed by using an etching hard cover, and thus it is possible to eliminate a photolithography operation.

(52) FIG. **12** is a perspective view of the etching hard cover **100**. As shown in FIG. **12**, the etching hard cover **100** has a rectangular frame shape having an opening corresponding to the pattern region PR of a phase shift photo mask. The etching hard cover **100** is made of a material that can endure the plasma etching of the light blocking layer (Cr contacting layer) **20**. In some embodiments, the etching hard cover is made of ceramic. Ceramic material includes, for example, but not limited to, boron nitride, alumina, silicon nitride (crystalline), silicon carbide, zirconia, and/or barium titanate. The ceramic material may be a sintered body. In other embodiments, glass or metallic material can be used for the etching hard cover **100**. In some embodiments, the surface of the etching hard cover **100** is coated with a coating material such as a silicon oxide, silicon nitride or any other material durable to the etching gas for the light blocking layer **20**. The etching hard cover **100** is attachable to and detachable from the photo mask substrate **10** with films to be processed and is reusable.

(53) FIG. **13A** shows a cross sectional view corresponding to line A-A of FIG. **12** of a side frame of the etching hard cover **100**. The main cover portion **101** of the etching hard cover **100**, which is to be placed over the pattern region PR of the phase shift photo mask, has a thickness **T1** in a range from about 0.3 mm to about 0.8 mm in some embodiments. In some embodiments, the etching hard cover **100** is placed on the photo mask in contact with the light blocking layer **20** at the border region BR, as shown in FIG. **13A**. The space **S1** between the lower surface of the main cover portion **101** of the etching hard cover **100** and the upper surface of the light blocking layer **20** is in a range from about 0.3 mm to about 0.8 mm in some embodiments. Accordingly, the side frame to be in contact with the upper surface of the light blocking layer **20** has a thick portion having a thickness **T3** ($=T1+S1$) in a range from about 0.6 mm to about 1.6 mm in some embodiments. The side end portion **103** (skirt portion) has a thickness **T2** in a range from about 0.3 mm to about 0.8 mm in some embodiments.

(54) As shown in FIG. **13A**, the etching hard cover **100** is in direct contact with the upper surface

of the light blocking layer **20** at the border region BR. The width W2 of the area at which the etching hard cover **100** is in direct contact with the upper surface of the light blocking layer **20** is in a range about 10% to about 90% of the width W3 of the border region BR, and is in a range about 20% to about 80% of the width W3 of the border region BR, in other embodiments.

(55) In other embodiments, as shown in FIG. **13B**, the etching hard cover **100** does not directly contact with the upper surface of the photo mask (the upper surface of the light blocking layer **20**). For example, a skirt portion **104** of the etching hard cover **100** has a long dimension such that the bottom of the etching hard cover **100** is placed on a mask stage **200** of an etching apparatus, on which the photo mask is placed.

(56) FIG. **13C** shows another embodiment of the etching hard cover **100**. In this embodiment, the lower surface of the main cover portion **101** of the etching cover **100** includes an abutting portion, for example, a protrusion **110** that contacts the upper surface of the light blocking layer **20** at the border region BR. The position W4 of the protrusion **110** is in a range about 10% to about 90% of the width W3 of the border region BR in some embodiments, and in a range about 20% to about 50% of the width W3 of the border region BR in other embodiments. In the case of the protrusion, it is possible to minimize the contact area of the etching hard cover **100** to the surface of the light blocking layer **20**. In other embodiments, a protrusion similar to the protrusion **110** is formed at the inside surface of the skirt portion **102** to be in contact with the side face of the mask substrate **10**. In certain embodiments, the shape of the etching hard cover **100** shown in FIG. **13A** and the protrusion **110** shown in FIG. **13C** are combined.

(57) FIG. **13D** shows another embodiment of the etching hard cover **100**. In this embodiment, instead of a protrusion shown in FIG. **13C**, an O-ring **120** embedded in a groove formed on the lower surface of the main cover portion **101** in contact with the upper surface of the light blocking layer **20** at the border region BR is used.

(58) The position W4 of the center of the O-ring **120** (groove) is in a range about 10% to about 90% of the width W3 of the border region BR in some embodiments, and in a range about 20% to about 50% of the width W3 of the border region BR in other embodiments. The O-ring **120** is made of, for example, but not limited to, rubber (e.g., butadiene rubber, butyl rubber, ethylene propylene diene monomer rubber, or nitrile rubber), polytetrafluoroethylene (PTFE), perfluoroelastomer, or silicone. Similar to the protrusion **110**, the use of the O-ring **120** can minimize the contact area of the etching hard cover **100** to the surface of the light blocking layer **20**. In other embodiments, a second O-ring **125** is embedded in a groove formed on the inside surface of the skirt portion **103** and contacts the side face of the mask substrate **10**. When the second O-ring **125** is used, it is not necessary for the skirt portion **103** to be in contact with the mask stage **200**. In some embodiments, only the second O-ring **125** is used. In certain embodiments, the shape of the etching hard cover **100** shown in FIG. **13A** and the first O-ring **120** and/or the second O-ring **125** shown in FIG. **13C** are combined.

(59) FIGS. **14-24** show various stages for a sequential manufacturing process of a phase shift photo mask according to another embodiment of the present disclosure. It is understood that in the sequential manufacturing process, one or more additional operations can be provided before, during, and after the stages shown in the drawings, and some of the operations described below can be replaced or eliminated for additional embodiments of the method. The order of the operations/processes may be interchangeable. Materials, configurations, dimensions and/or processes the same as or similar to the foregoing embodiments described by FIGS. **1-13D** may be employed in the following embodiments, and detailed explanation thereof may be omitted.

(60) First, a mask blank **10** is provided. The mask blank or a mask substrate **10** is made of a material transparent to deep ultra violet light (e.g., 245 nm light emitted from a KrF excimer laser or 193 nm light emitted from an ArF excimer laser). In some embodiments, the mask substrate **10** is made of quartz. In certain embodiments, a quartz mask substrate according to 6025 SEMI standard is used for the mask substrate **10**.

(61) As shown in FIG. 14, a phase shift layer 15 is formed on the mask substrate 10 and a light blocking layer 20 is formed on the phase shift layer 15. The phase shift layer may also be referred to as a light attenuating layer. The phase shift layer 15 has a material and sufficient thickness to pass from about 4% to about 40% of incident light with a phase shift of the transmitted light of about 180 degrees. In some embodiments, the phase shift layer 15 is made of, for example, but not limited to, at least one layer of MoSi, molybdenum silicon nitride (MoSi.sub.xN.sub.y) and molybdenum silicon oxynitride ($\text{MoSi.sub.xO.sub.yN.sub.z}$). In other embodiments, the phase shift layer 15 is made of a silicon nitride based material, such as silicon nitride, silicon oxynitride, silicon carbo-nitride and/or silicon carbo-oxide. The phase shift layer 15 can be a mono-layer or include two or more layers. In some embodiments, the phase shift layer 15 has a thickness of from about 50 nm to about 150 nm, depending on the optical properties of the material and the thickness required to retard the phase of transmitted light about 180 degrees. The phase shift layer 15 can be formed by ion beam deposition (IBD), atomic layer deposition (ALD), chemical vapor deposition (CVD), or physical vapor deposition (PVD) (sputtering).

(62) The light blocking layer 20 is substantially opaque (non-transmitting) to incident light, for example, deep ultra violet light. In some embodiments, the light blocking layer 20 is a chromium containing layer, for example formed of at least one layer of Cr, chromium oxynitride (CrO.sub.xN.sub.y) and chromium nitride (CrN.sub.x), having a thickness less than about 50 nm to about 200 nm. The light blocking layer 20 can be formed by a sputtering method or other suitable film forming method.

(63) As shown in FIG. 14, in this embodiment, a hard mask layer 25 is formed on the light blocking layer 20. The hard mask layer 25 is made of, for example, but not limited to, a silicon oxide based material or a silicon nitride based material. In some embodiments, silicon oxide or oxygen deficient silicon oxide (SiO.sub.x) is used. A thickness of the hard mask layer 25 is in a range from about 10 nm to about 100 nm in some embodiments. The hard mask layer 25 can be formed by ion beam deposition (IBD), atomic layer deposition (ALD), chemical vapor deposition (CVD), or physical vapor deposition (PVD) (sputtering).

(64) Further, as shown in FIG. 14, a first photo resist layer 30 is formed over the hard mask layer 25. Before the first photo resist layer 30 is formed, the photo mask blank with the phase shift layer 15, the light blocking layer 20 and the hard mask layer 25 is subject to inspection. Then, the first photo resist layer 30 is exposed with an electron beam according to a layout design having desired circuit patterns. FIG. 15 shows a cross sectional view after the exposed first photo resist layer 30 is developed with a developing solution. In some embodiments, after the development of the photo resist layer first, a post baking operation to harden the developed photo resist pattern 35 is performed.

(65) Further, by using the photo resist pattern 35 as an etching mask, the hard mask layer 25 is etched to form a hard mask pattern 38. The etching of the hard mask layer 25 can be performed by dry etching and/or wet etching in some embodiments. After the hard mask layer 25 is etched, the photo resist pattern 35 is removed by appropriate removal and cleaning operations, as shown in FIG. 16.

(66) Subsequently, by using the hard mask pattern 38 as an etching mask, the light blocking layer 20 is etched, to form a pattern 36, as shown in FIG. 17. The etching of the light blocking layer 20 can be performed by dry etching and/or wet etching in some embodiments.

(67) After the light blocking layer 20 is etched, the hard mask pattern 38 is removed by appropriate removal and cleaning operations, as shown in FIG. 18. In some embodiments, the surface of the phase shift layer 15 is slightly etched when removing the hard mask pattern 38.

(68) Next, as shown in FIG. 19, by using the pattern 36 formed by the light blocking layer 20 as an etching mask, the phase shift layer 15 is etched, to form a phase shift pattern 37. The etching of the phase shift layer 15 can be performed by dry etching and/or wet etching in some embodiments. After the etching, a cleaning operation is performed in some embodiments.

(69) Subsequently, an etching hard cover **100** is placed over the photo mask as shown in FIG. **20**. The etching hard cover **100** is a separately prepared piece and placed on or over the photo mask. The etching hard cover **100** covers the opaque border region BR and has an opening over the pattern region PR.

(70) By using the etching hard cover **100** as an etching mask, the light blocking layer **20** in the pattern region PR is removed. As shown in FIG. **21**, the etching hard cover **100** covers a part of the pattern region PR in some embodiments. Thus, the light blocking layer **20** located under the etching hard cover **100** in the pattern region PR is not etched, forming residues **22**. After the light blocking layer **20** in the pattern region PR is etched, the etching hard cover **100** is removed and a cleaning operation is performed in some embodiments.

(71) Subsequently, a second photo resist layer **40** is coated on the patterned photo mask, and a lithography operation using electron beam lithography or optical lithography and a resist development operation are performed. As shown in FIG. **22**, the second photo resist pattern **40** is formed on the light blocking layer **20** remaining at the opaque border region BR.

(72) Then, as shown in FIG. **23**, by using the second photo resist pattern **40** formed on the border region BR as an etching mask, the light blocking layer **22** (residues) remaining on the phase shift layer **15** at the pattern region PR is etched. The etching of the light blocking layer **22** can be performed by dry etching in some embodiments. Then, the second photo resist pattern **40** is removed by an appropriate resist removal operation, as shown in FIG. **24**. After the etching, a cleaning operation is performed in some embodiments.

(73) After the cleaning operation, an inspection operation is performed to detect residues of the light blocking layer (e.g., Cr residues). When unacceptable Cr residues (e.g., size and/or amount of Cr residues) are found, the phase shift photo mask will undergo one or more additional photolithography and etching operations similar to the operations with respect to FIGS. **22** and **23**. The additional Cr removal operation and the inspection operation may be repeated until no Cr residue (or Cr defect) is found or the detected Cr residues are below the threshold size and/or amount.

(74) In the foregoing embodiment, the light blocking layer **20** in the pattern region PR is first “roughly” etched and removed by using an etching hard cover, and thus it is possible to eliminate a photolithography operation.

(75) It will be understood that not all advantages have been necessarily discussed herein, no particular advantage is required for all embodiments or examples, and other embodiments or examples may offer different advantages.

(76) For example, by using a detachable etching hard cover in the etching operation for the light blocking layer (Cr containing layer) in the pattern region, while covering the border region, it is possible to eliminate at least one lithography operation including resist coating, exposure and development of the exposed resist during a manufacturing operation of an attenuated phase shift photo mask. Further, it is possible to effectively remove the light blocking layer and its residues from the pattern region.

(77) In accordance with an aspect of the present disclosure, in a method of manufacturing a photo mask, a photo resist layer is formed over a mask blank, which includes a mask substrate, a phase shift layer disposed on the mask substrate and a light blocking layer disposed on the phase shift layer. A photo resist pattern is formed by using a lithographic operation. The light blocking layer is patterned by using the photo resist pattern as an etching mask. The phase shift layer is patterned by using the patterned light blocking layer as an etching mask. A border region of the mask substrate, on which part of the light blocking layer remains, is covered with an etching hard cover, while a pattern region of the mask substrate is exposed through an opening of the etching hard cover. The patterned light blocking layer in the pattern region is patterned through the opening of the etching hard cover. The etching hard cover is detached. A photo-etching operation is performed on the pattern region to remove residues of the light blocking layer. In one or more of the foregoing and

following embodiments, the etching hard cover is reusable. In one or more of the foregoing and following embodiments, the etching hard cover is made of ceramic. In one or more of the foregoing and following embodiments, the etching hard cover has a frame shape having the opening and a frame portion defining the opening. In one or more of the foregoing and following embodiments, the frame portion covers the border region. In one or more of the foregoing and following embodiments, the frame portion partially covers the pattern region. In one or more of the foregoing and following embodiments, the phase shift layer include one or more layers of molybdenum silicide, molybdenum silicon nitride, and molybdenum silicon oxynitride. In one or more of the foregoing and following embodiments, after performing the photo-etching operation, the pattern region is inspected. When an inspecting result is undesirable, repeating the photo-etching operation on the pattern region and the inspecting until a desirable inspecting result is obtained. In one or more of the foregoing and following embodiments, the border region of the mask substrate is covered by the etching hard cover such that the etching hard cover is in contact with the light blocking layer at the border region. In one or more of the foregoing and following embodiments, the border region of the mask substrate is covered by the etching hard cover such that the etching hard cover is not in contact with the light blocking layer at the border region. In one or more of the foregoing and following embodiments, the border region of the mask substrate is covered by the etching hard cover such that the etching hard cover is in contact with the mask substrate.

(78) In accordance with another aspect of the present disclosure, in a method of manufacturing a photo mask, a photo resist layer is formed over a mask blank, which includes a mask substrate, a phase shift layer disposed on the mask substrate, a light blocking layer disposed on the phase shift layer and a hard mask layer disposed on the light blocking layer. A photo resist pattern is formed by using a lithographic operation. The hard mask layer is patterned by using the photo resist pattern as an etching mask. The light blocking layer is patterned by using the patterned hard mask layer as an etching mask. The phase shift layer is patterned by using the patterned light blocking layer as an etching mask. A border region of the mask substrate, on which part of the light blocking layer remains, is covered with an etching hard cover, while a pattern region of the mask substrate is exposed through an opening of the etching hard cover. The patterned light blocking layer in the pattern region is etched through the opening of the etching hard cover. The etching hard cover is detached. A photo-etching operation is performed on the pattern region to remove residues of the light blocking layer. In one or more of the foregoing and following embodiments, the etching hard cover is reusable. In one or more of the foregoing and following embodiments, the etching hard cover is made of ceramic. In one or more of the foregoing and following embodiments, the etching hard cover has a frame shape having the opening and a frame portion defining the opening. In one or more of the foregoing and following embodiments, the frame portion fully covers the border region, and partially covers the pattern region. In one or more of the foregoing and following embodiments, the border region of the mask substrate is covered by the etching hard cover such that the etching hard cover is in contact with the light blocking layer at the border region. In one or more of the foregoing and following embodiments, the border region of the mask substrate is covered by the etching hard cover such that the etching hard cover is not in contact with the light blocking layer at the border region. In one or more of the foregoing and following embodiments, the border region of the mask substrate is covered by the etching hard cover such that the etching hard cover is in contact with the mask substrate.

(79) In accordance with another aspect of the present disclosure, an etching hard cover for a photo mask manufacturing operation is made of ceramic, and has a frame shape having the opening and a frame portion defining the opening. The frame portion includes a main cover portion that covers a border region of the photo mask to be manufactured. A bottom surface of the main cover portion includes an abutting portion to abut the photo mask, when the etching hard cover is placed on the photo mask.

(80) The foregoing outlines features of several embodiments or examples so that those skilled in

the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments or examples introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A method, comprising: forming a photo resist layer over a mask blank, which includes a mask substrate, a phase shift layer disposed on the mask substrate and a light blocking layer disposed on the phase shift layer; forming a photo resist pattern by using a lithographic operation; patterning the light blocking layer by using the photo resist pattern as an etching mask; patterning the phase shift layer by using the patterned light blocking layer as an etching mask; covering a border region of the mask substrate, on which the patterned light blocking layer remains, with a sintered body etching hard cover, which does not include an O-ring, while a pattern region of the mask substrate is exposed through an opening of the sintered body etching hard cover, wherein the sintered body etching hard cover is in direct contact with an uppermost surface of patterned light blocking layer in the border region; etching the patterned light blocking layer in the pattern region through the opening of the sintered body etching hard cover; and performing a photo-etching operation on the pattern region to remove residues of the light blocking layer.
2. The method of claim 1, wherein the sintered body etching hard cover comprises at least one of boron nitride, alumina, crystalline silicon nitride, silicon carbide, zirconia, and barium titanate, or a coating of silicon oxide or silicon nitride.
3. The method of claim 1, wherein the sintered body etching hard cover has a frame shape having the opening and a frame portion defining the opening.
4. The method of claim 3, wherein the frame portion covers the border region or partially covers the pattern region.
5. The method of claim 1, wherein the phase shift layer includes one or more layers of molybdenum silicide, molybdenum silicon nitride, and molybdenum silicon oxynitride.
6. The method of claim 1, further comprising, after performing the photo-etching operation, inspecting the pattern region, wherein when an inspecting result is undesirable, repeating the photo-etching operation on the pattern region and the inspecting until a desirable inspecting result is obtained.
7. The method of claim 1, wherein the phase shift layer comprises silicon nitride, silicon oxynitride, silicon carbo-nitride, silicon carbo-oxide, chromium oxide, chromium oxynitride, or chromium nitride.
8. The method of claim 1, wherein the border region of the mask substrate is covered by the sintered body etching hard cover such that the sintered body etching hard cover is in contact with the mask substrate.
9. A phase shift photo mask manufacturing process, comprising: forming a patterned light blocking layer over a light attenuating layer of a phase shift photo mask; placing an etching hard cover over the phase shift photo mask and a mask stage of an etching apparatus such that: a border region of the phase shift photo mask is covered with the etching hard cover, wherein the etching hard cover includes a rectangular frame that defines a rectangular opening and the rectangular frame includes a first portion and a second portion longer than the first portion and extending transversely from the first portion, and the etching hard cover is placed over the mask stage, wherein a bottom surface of the first portion faces the phase shift photo mask and includes a protrusion made of the same material as the etching hard cover that provides a gap between the etching hard cover and the

patterned light blocking layer, wherein a side surface of the second portion contacts the patterned light blocking layer, and wherein the protrusion made of the same material as the etching hard cover is in direct contact with an uppermost surface of the patterned light blocking layer in the border region; and etching the patterned light blocking layer through the rectangular opening of the etching hard cover.

10. The phase shift photo mask manufacturing process of claim 9, wherein the etching hard cover comprises at least one of boron nitride, alumina, crystalline silicon nitride, silicon carbide, zirconia, and barium titanate, or a coating of silicon oxide or silicon nitride.

11. The phase shift photo mask manufacturing process of claim 9, wherein the light attenuating layer includes one or more layers of molybdenum silicide, molybdenum silicon nitride, and molybdenum silicon oxynitride.

12. The phase shift photo mask manufacturing process of claim 9, wherein the rectangular frame covers at least the border region.

13. The phase shift photo mask manufacturing process of claim 9, wherein the gap between the etching hard cover and the patterned light blocking layer extends along the border region.

14. The phase shift photo mask manufacturing process of claim 9, wherein the side surface of the second portion contacts a side surface of the light attenuating layer.

15. The phase shift photo mask manufacturing process of claim 9, wherein the light attenuating layer comprises silicon nitride, silicon oxynitride, silicon carbo-nitride, silicon carbo-oxide, chromium oxide, chromium oxynitride, or chromium nitride.

16. The phase shift photo mask manufacturing process of claim 9, wherein the etching hard cover includes glass or metallic material.

17. The phase shift photo mask manufacturing process of claim 9, wherein the light attenuating layer is formed by ion beam deposition (IBD), atomic layer deposition (ALD), chemical vapor deposition (CVD), or physical vapor deposition (PVD).

18. A phase shift photo mask manufacturing process, comprising: forming a patterned light blocking layer over a light attenuating layer of a phase shift photo mask; placing an etching hard cover over the phase shift photo mask and a mask stage of an etching apparatus such that: a border region of the phase shift photo mask is covered with the etching hard cover, wherein the etching hard cover includes a rectangular frame that defines a rectangular opening and the rectangular frame includes a first portion and a second portion longer than the first portion and extending transversely from the first portion, and the etching hard cover is placed to cover the mask stage, wherein a bottom surface of the first portion faces the phase shift photo mask and includes an abutting portion made of the same material as the etching hard cover, the abutting portion provides a gap between the etching hard cover and the patterned light blocking layer, the abutting portion made of the same material as the etching hard cover of the first portion is in direct contact with an uppermost surface of the patterned light blocking layer in the border region, and a side surface of the second portion contacts the patterned light blocking layer and the light attenuating layer; and etching the patterned light blocking layer through the rectangular opening of the etching hard cover.

19. The phase shift photo mask manufacturing process of claim 18, wherein the light attenuating layer comprises silicon nitride, silicon oxynitride, silicon carbo-nitride, silicon carbo-oxide, chromium oxide, chromium oxynitride, or chromium nitride.

20. The phase shift photo mask manufacturing process of claim 18, wherein the etching hard cover includes glass or metallic material.
