

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12414243
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Yang; Kai-Ming et al.

Manufacturing method of package structure

Abstract

A method of manufacturing package structure includes following steps. An insulating composite layer is formed on a metal layer of a carrier board. A chip packaging module including a sealant and a first chip embedded therein is disposed on the insulating composite layer, in which the first chip has a plurality of conductive pads. A first circuit layer module including a dielectric layer and a circuit layer is formed on the chip packaging module, in which the circuit layer is on the dielectric layer and electrically connected to the conductive pads through a conductive vias in the dielectric layer. A second chip is disposed on the first circuit layer module. A second circuit layer module is formed on the first circuit layer module and the second chip. A protecting layer is formed on the second circuit layer module.

Inventors: Yang; Kai-Ming (Hsinchu County, TW), Lin; Chen-Hao (Keelung, TW), Ko; Cheng-Ta (Taipei, TW), Lau; John Hon-Shing (New Territories, HK), Chen; Yu-Hua (Hsinchu, TW), Tseng; Tzyy-Jang (Hsinchu, TW)

Applicant: Unimicron Technology Corp. (Taoyuan, TW)

Family ID: 67392987

Assignee: Unimicron Technology Corp. (Taoyuan, TW)

Appl. No.: 17/818006

Filed: August 08, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20220375919 A1	Nov. 24, 2022

Foreign Application Priority Data

TW	100139667	Oct. 31, 2011
TW	105133848	Oct. 20, 2016
TW	106123710	Jul. 14, 2017

Related U.S. Application Data

continuation-in-part parent-doc US 15701435 20170911 ABANDONED child-doc US 16379816
continuation-in-part parent-doc US 15391861 20161228 US 11127664 20210921 child-doc US
15701435

continuation-in-part parent-doc US 14602656 20150122 US 9781843 20171003 child-doc US
15391861

division parent-doc US 16379816 20190410 US 11445617 child-doc US 17818006

division parent-doc US 13604968 20120906 US 8946564 20150203 child-doc US 14602656

Publication Classification

Int. Cl.: **H05K3/40** (20060101); **H01L21/48** (20060101); **H01L21/768** (20060101); **H01L23/00**
(20060101); **H01L23/14** (20060101); **H01L23/15** (20060101); **H01L23/498** (20060101);
H01L23/538 (20060101); **H01L25/00** (20060101); **H05K1/11** (20060101); **H05K1/14**
(20060101); **H05K1/18** (20060101); **H05K3/32** (20060101); **H05K3/46** (20060101)

U.S. Cl.:

CPC **H05K3/4038** (20130101); **H01L21/4846** (20130101); **H01L21/4857** (20130101);
H01L21/486 (20130101); **H01L21/76898** (20130101); **H01L23/145** (20130101);
H01L23/147 (20130101); **H01L23/15** (20130101); **H01L23/49822** (20130101);
H01L23/49827 (20130101); **H01L23/5383** (20130101); **H01L23/5384** (20130101);
H01L23/5389 (20130101); **H01L24/83** (20130101); **H01L25/50** (20130101); **H05K1/11**
(20130101); **H05K1/112** (20130101); **H05K1/142** (20130101); **H05K1/183** (20130101);
H05K3/32 (20130101); **H05K3/4682** (20130101); H01L23/49816 (20130101);
H01L2224/131 (20130101); H01L2224/16225 (20130101); H01L2224/16237
(20130101); H01L2224/32225 (20130101); H01L2224/73204 (20130101);
H01L2224/8385 (20130101); H01L2924/00014 (20130101); H01L2924/014 (20130101);
H01L2924/15311 (20130101); H05K1/185 (20130101); H05K2201/10674 (20130101);
H05K2203/1469 (20130101); Y10T29/4913 (20150115); Y10T29/49146 (20150115);
Y10T29/49165 (20150115); H01L2224/73204 (20130101); H01L2224/16225
(20130101); H01L2224/32225 (20130101); H01L2924/00 (20130101)

Field of Classification Search

CPC: H01L (21/4846); H01L (21/4857); H01L (21/486); H01L (21/76898); H01L (23/145);
H01L (23/147); H01L (23/15); H01L (23/49822); H01L (23/49827); H01L (23/5383);
H01L (23/5384); H01L (23/5389); H01L (24/83); H01L (2224/131); H01L (2224/16225);
H01L (2224/16237); H01L (2224/32225); H01L (2224/73204); H01L (2224/8385); H01L
(2924/00014); H01L (2924/014); H01L (2924/15311); H01L (23/49816); H05K (3/4038);
H05K (3/32); H05K (3/4682); H05K (2203/1469); H05K (1/11); H05K (1/112); H05K
(1/142); H05K (1/183); H05K (1/185); H05K (2201/10674)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2014/0327150	12/2013	Jung	257/774	H01L 21/76898

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2010212683	12/2009	JP	H01L 23/5383

OTHER PUBLICATIONS

Davies et al, "Process and technology choices for manufacturing high density interconnections on silicon substrates for multichip modules," 12th International Electronic Manufacturing Technology Symposium, Mainz, Germany, 1992, pp. 286-293. (Year: 1992). cited by examiner

Primary Examiner: Tugbang; A. Dexter

Attorney, Agent or Firm: CKC & Partners Co., LLC

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION (1) This application is a divisional of the U.S. application Ser. No. 16/379,816, filed Apr. 10, 2019, which is a continuation-in-part of U.S. application Ser. No. 15/701,435, filed Sep. 11, 2017, which is a continuation-in-part of U.S. application Ser. No. 15/391,861, filed Dec. 28, 2016, now patented as U.S. Pat. No. 11,127,664, issued Sep. 21, 2021, which is a continuation-in-part of U.S. application Ser. No. 14/602,656, filed Jan. 22, 2015, now patented as U.S. Pat. No. 9,781,843, issued Oct. 3, 2017, which is a divisional of U.S. application Ser. No. 13/604,968, filed Sep. 6, 2012, now patented as U.S. Pat. No. 8,946,564, issued Feb. 3, 2015. The prior U.S. application Ser. No. 16/379,816 claims priority to Taiwan Application Serial Number 107112303, filed Apr. 10, 2018. The prior U.S. application Ser. No. 15/701,435 claims priority to Taiwan Application serial number 106123710, filed Jul. 14, 2017. The prior U.S. application Ser. No. 15/391,861 claims priority to Taiwan Application serial number 105133848, filed Oct. 20, 2016. The prior U.S. application Ser. No. 13/604,968 claims priority to Taiwan Application serial number 100139667, filed Oct. 31, 2011. The entirety of each of the above-mentioned patent applications is hereby incorporated by reference herein and made a part of this specification.

BACKGROUND

Field of Invention

(1) The present disclosure relates to a package structure and a manufacturing method thereof.

Description of Related Art

(2) Along with the advancement in semiconductor packaging technology, there have been various types of packages for semiconductor devices developed besides the conventional wire bonding semiconductor packaging technique. For example, one type of semiconductor devices allows a semiconductor chip having an integrated circuit (IC) to be embedded in and electrically integrated with a package substrate in order to reduce the overall dimension and improve the electrical functions. In order to satisfy the demands of shortening the wire length, reducing the overall

thickness, and requirements of high-frequency and miniaturization, a method of processing a chip substrate embedded on a carrier board without a coreless layer has been developed.

(3) However, since the carrier board without a coreless layer lacks a hard core plate for supporting, the carrier board is prone to warpage due to insufficient structural strength. In addition, as the number of chips to be disposed on a planar package substrate (such as a germanium substrate) increases, they can obstruct the downsizing of the package structure and occupy too much area, resulting in a rising manufacturing cost, which is undesired to the application of portable electronic products.

SUMMARY

(4) One purpose of the present disclosure is to provide a manufacturing method of a package structure which may address the abovementioned issues.

(5) To achieve the foregoing purpose, one aspect of the present disclosure is to provide a method of manufacturing a package structure. The method includes steps of: providing a carrier board comprising a supporting layer, a first release layer, a second release layer and a plurality of metal layer, in which the first release layer and the second release layer is disposed on opposite surfaces of the supporting layer respectively, and the metal layers are disposed on the first release layer and the second release layer; forming an insulating composite layer on the metal layer; disposing a chip packaging module on the insulating composite layer, in which the chip packaging module includes a sealant and a first chip embedded therein, the first chip has a plurality of first conductive pads exposed through the sealant; forming a first circuit layer module on the chip packaging module, in which the first circuit layer module comprises at least one first dielectric layer and at least one first circuit layer, the first dielectric layer has a plurality of first conductive vias, the first circuit layer is located on the first dielectric layer and in contact with the first conductive vias, in which the first circuit layers is electrically connected to the first conductive pads through the first conductive vias; disposing a second chip on the first circuit layer module, the second chip having a plurality of second conductive pads; forming a second circuit layer module on the first circuit layer module and the second chip, in which the second circuit layer module comprises at least one second dielectric layer and at least one second circuit layers, the second dielectric layer has a plurality of second conductive vias, the second circuit layer is located on the second dielectric layer and in contact with the second conductive vias, in which the second circuit layers is electrically connected to the second conductive pads through the second conductive vias; and forming a protecting layer on the second circuit layer module, in which the protecting layer has a plurality of openings exposing a portion of the second circuit layer module.

(6) According to one embodiment of the present disclosure, the at least one first dielectric layer may comprise a plurality of first dielectric layers, while the at least one first circuit layer may comprise a plurality of first circuit layers.

(7) According to one embodiment of the present disclosure, the step of disposing the second chip on the first circuit layer module further includes disposing the second chip on the uppermost first circuit layer of the first circuit layer module.

(8) According to one embodiment of the present disclosure, the step of disposing the second chip on the first circuit layer module comprises disposing an adhesive layer between the uppermost first circuit layer and the second chip.

(9) According to one embodiment of the present disclosure, the method further includes disposing a third chip on the uppermost first dielectric layer of the first circuit layer module.

(10) According to one embodiment of the present disclosure, the first chip has a first surface and a second surface opposite thereto. The first conductive pads are exposed through the first surface, while the second surface is covered by the sealant.

(11) According to one embodiment of the present disclosure, the insulating composite layer comprises a composite having an inorganic insulating material and an organic material.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) The disclosure can be more fully understood by reading the following detailed description of the embodiment, with reference made to the accompanying drawings as follows.
- (2) FIG. 1 illustrates a flow chart of a method of manufacturing a package structure according to one embodiment of the present disclosure.
- (3) FIG. 2 through FIG. 9 illustrates schematic cross-sectional views of a package structure during various processing stages according to some embodiments of the present disclosure.
- (4) FIG. 10 through FIG. 12 illustrates cross-sectional views of a package structure according to other embodiments of the present disclosure.

DETAILED DESCRIPTION

- (5) The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. The examples disclosed below may be combined or substituted with each other in a beneficial situation, and other examples may be added to an example without further description or explanation.
- (6) In the following description, specific details are set forth in the description. However, examples of one of the present disclosures may be practiced without such specific details. Furthermore, for simplifying the drawings, some of the conventional structures and elements are shown with schematic illustrations.
- (7) One aspect of the present disclosure is to provide a method of manufacturing a package structure. The package structure formed thereof may have a higher reliability and chip integration density that meets requirements of miniaturization and high processing speed. FIG. 1 illustrates a flow chart of a method 10 of manufacturing a package structure 100 according to one embodiment of the present disclosure. FIG. 2 through FIG. 9 illustrates schematic cross-sectional views of a package structure 100 during various processing stages of a method 10 according to some embodiments of the present disclosure. As shown in FIG. 1, the method 10 includes step S01 to step S07.
- (8) At step S01, a carrier board 110 as shown in FIG. 2 is provided. Specifically, the carrier board 110 includes a supporting layer 112, a first release layer 114, a second release layer 116, and a plurality of metal layers 118. The first release layer 114 is disposed on one surface of the supporting layer 112, and the second release layer 116 is disposed on the opposite surface of the supporting layer 112. The metal layers 118 are disposed on each of the first release layer 114 and the second release layer 116. In some embodiments, the supporting layer 112 may be made of a polymeric material such as bismaleimide triazine (BT). In some embodiments, the supporting layer 112 may be a copper clad laminate (CCL) (not shown) with a dielectric material (for example, a prepreg) disposed thereon. In some embodiments, the first release layer 114 or the second release layer 116 may be a release film. In other embodiments, the first release layer 114 or the second release layer 116 may be a copper foil bonded with a release layer available from Mitsui, Nippon-Denk, Furukawa or Olin, for example. In some embodiments, a thickness of the metal layer 118 may range from 1 μm to 10 μm , but is not limited thereto. The metal layers 118 may be made of copper, aluminum, nickel, silver, gold or an alloy thereof, but is not limited thereto. In other embodiments, the metal layers 118 may be a single layer or a stack of a plurality of metal layers 118.
- (9) In other embodiments, an additional metal layer (not shown) may exist between the supporting layer 112 and the first release layer 114 and/or between the supporting layer 112 and the second release layer 116. A thickness of the metal layer may range from 5 μm to 40 μm . The additional

metal layer and the metal layer **118** may be made of the same material or different material, such as copper, aluminum, nickel, silver, gold, or an alloy thereof, but is not limited thereto.

(10) At step **S02**, an insulating composite layer **120** is formed on each metal layer **118**, as shown in FIG. **3**. It is understood that the step **S02** and following step **S03** to step **S07** may be performed on a single surface or both opposite surfaces of the carrier board **110**. In the present embodiment, a double-sided fabrication of the carrier board **110** is described. In some embodiments, the insulating composite layer **120** comprises a composite having an inorganic insulating material and an organic material. In detail, the inorganic insulating material may include a ceramic material, such as zirconium dioxide, silicon carbide, silicon nitride, aluminum oxide, silicon oxide or a combination thereof, and the organic material may include a polymer, such as epoxy resins, polyimides, liquid crystal polymers, methacrylate resins, polyacrylate resins, allyl resins, vinyl phenyl resins, polysiloxane resins, polyolefin resins, polyurethane resins, polyether resins, or a combination thereof. In one example, the ceramic material may be ceramic flakes, ceramic powder, ceramic microparticles, or ceramic nanoparticles, but is not limited thereto.

(11) In an example where the inorganic insulating material is ceramic powder, the insulating composite layer **120** may be made by impregnating the ceramic powder in a polymer using a vacuum impregnation technique to prepare the insulating composite layer **120**, which is a composite consisting of the ceramic powder and polymer. In an example where the polymer is epoxy resins or polyimide resins, the insulating composite layer **120** is disposed on the metal layers **118** by a thermal bonding process, a vacuum impregnation technique with a follow-up UV irradiation and heating process.

(12) In an example where the inorganic insulating material is ceramic flake, the insulating composite layer **120** may be made by impregnating the ceramic flake in a polymer using a vacuum impregnation technique to prepare the insulating composite layer **120**, which is a composite consisting of the ceramic flake and polymer. However, the insulating composite layer **120** of the present example can be prepared by other techniques capable of forming the insulating composite layer **120** consisting of a polymer and a ceramic material. In an example where the inorganic insulating material is ceramic flake, the insulating composite layer **120** comprises an organic matter and an inorganic matter (for example, a polymer and ceramic flakes). Due to the adhesion between the organic matter and the inorganic matter, the ceramic flake of the insulating composite layer **120** has a sheet-like or a brick-like (or a combination thereof) laminated microscopic structure, which suppresses the conduction of the lateral breaking force, resulting in significant increase of hardness. Thus, the ceramic flake is relatively hard and has a high elasticity modulus, thereby increasing the strength, brittleness and toughness of the ceramic. In yet another example, the insulating composite layer **120** may be an imitation nacreous layer.

(13) The Young's modulus of the insulating composite layer **120** may range from 20 GPa to 100 GPa. Compared with conventional dielectric layers (with Young's modulus not more than 10 GPa) and conventional packaging material (with Young's modulus not more than 20 GPa), the insulating composite layer **120** of the present example has an excellent hardness which can enhance the structural strength of the package structure.

(14) At step **S03**, a chip packaging module **20** is disposed on the insulating composite layer **120**, as shown in FIG. **4**. Specifically, the chip packaging module **20** may be disposed on two opposite surfaces of the insulating composite layer **120**. The chip packaging module **20** includes a sealant **130** and a first chip **140** embedded therein. The first chip **140** includes a plurality of the first conductive pads **144** and a chip substrate **142**. The first conductive pads **144** are exposed through the sealant **130**. In some embodiments, the first chip **140** has a first surface **140a** and a second surface **140b** opposite thereto. The first conductive pads **144** are exposed through the first surface **140a**, while the second surface **140b** is covered by the sealant **130**. The first conductive pad **144** includes a bottom portion **144b** below the first surface **140a** of the first chip **140** and at least one top portion **144t** over the first surface **140a** of the first chip **140**. The top portion **144t** is in contact

with the bottom portion **144b**. The first chip **140** may be electronic components of various integrated circuits that including discrete components, active or passive elements, digital or analog circuits, ECM, DRAM, SRAM, optoelectronic devices, micro electro mechanical systems (MEMS), microfluidic systems, or physical sensors that measures the variation of some physical quantities such as heat, light, or pressure, RF circuits, accelerators, gyroscopes, micro actuators, surface acoustic component, pressure sensors, or the like, but is not limited thereto. The first chip **140** is shown schematically, the actual length, width, height and dimensions may vary depending on product requirements.

(15) In some embodiments, the chip packaging module **20** is disposed on the insulating composite layer **120** by using an adhesive layer (not shown). Specifically, the adhesive layer may be disposed on a bottom surface **20S** of the chip packaging module **20**, and the chip packaging module **20** is then disposed on the insulating composite layer **120**. In one example, the adhesive layer may include a heat sink with high heat dissipation or high-temperature resistance, but is not limited thereto.

(16) At step **S04**, a first circuit layer module **150** is formed on the chip packaging module **20**, as shown in FIG. **5**. Specifically, the first circuit layer module **150** includes at least one the first dielectric layer **152** and at least one the first circuit layers **154**. One skilled in the art can modify the number of the dielectric layers and circuit layers based on actual needs. It is understood that the smallest unit constituting the first circuit layer module **150** is one dielectric layer and one circuit layer. The first dielectric layer **152** has a plurality of the first conductive vias **156**. The first circuit layers **154** are disposed on the first dielectric layer **152** and in contact with the first conductive vias **156**. The bottommost first circuit layer **154** is electrically connected to the first conductive pads **144** of the first chip **14** through the first conductive vias **156**.

(17) In some embodiments, the first dielectric layer **152** may be made of resin and glass fiber. For example, the resin may be phenolic resins, epoxy resins, polyimide resins or a polytetrafluoroethylene. Alternatively, the first dielectric layer **152** may include a photo-imageable dielectric (PID). In some embodiments, the first dielectric layer **152** may be formed by a lamination process, a coating process or other suitable processes. In some embodiments, the blind holes for the formation of the first conductive vias **156** may be formed in the first dielectric layer **152** by using (but not limited to) a laser ablation process, otherwise an exposure and developing process if the first dielectric layer **152** is a photo-imageable dielectric.

(18) The method of forming the first circuit layers **154** according to a plurality of embodiments is briefly described below. First, a photoresist layer such as a dry film (not shown) is formed on the first dielectric layers **152**. The photoresist layer is patterned by a lithography process, such that a portion of the first dielectric layers **152** is exposed. Next, an electroplating process is performed, followed by removal of the photoresist layer, such that the first circuit layers **154** and the first conductive vias **156** are formed. In one example, the first circuit layers **154** and the first conductive vias **156** may be made of copper. In other embodiments, before the formation of the first circuit layers **154**, a seed layer (not shown) may be formed on the first dielectric layers **152**. The seed layer may be a single-layered structure or a multilayer structure composed of sub-layers of different materials, including a metal layer having a titanium layer and a copper layer thereon, a palladium-plated copper layer, or the like, but is not limited thereto. The seed layer may be formed by a physical process such as sputtering of titanium and copper, or a chemical process such as electroplating of titanium and copper, but is not limited thereto.

(19) At step **S05**, a second chip **160** is disposed on the first circuit layer module **150**, as shown in FIG. **6**. The second chip **160** has a plurality of second conductive pads **162**. The second chip **160** may be electronic components of various integrated circuits that including discrete components, active or passive elements, digital or analog circuits, ECM, DRAM, SRAM, optoelectronic devices, micro electro mechanical systems (MEMS), microfluidic systems, or physical sensors that measures the variation of some physical quantities such as heat, light, or pressure, RF circuits,

accelerators, gyroscopes, micro actuators, surface acoustic component, pressure sensors, or the like, but is not limited thereto. The second chip **160** is shown schematically, the actual length, width, height and dimensions may vary depending on product requirements.

(20) In one embodiment, the second chip **160** is disposed on the uppermost first circuit layers **154** of the first circuit layer module **150**. In some embodiments, the second chip **160** is disposed on the uppermost first circuit layers **154** of the first circuit layer module **150** by using an adhesive layer **168**. Specifically, the adhesive layer **168** is adhered to the bottom of the second chip **160**, followed by bonding the second chip **160** to the first circuit layers **154**. Alternatively, the adhesive layer **168** is adhered to the first circuit layers **154**, followed by bonding the second chip **160** to the adhesive layer **168**. In one example, the adhesive layer **168** may include a heat sink with a high heat dissipation or high-temperature resistance, but is not limited thereto. In another embodiment, a third chip **164** may be disposed on the uppermost first dielectric layer **152** of the first circuit layer module **150**. In some embodiments, the third chip **164** is disposed on the uppermost first dielectric layer **152** of the first circuit layer module **150** by a thermal bonding process. It is understood that the third chip **164** and the second chip **160** may be the same or different. The third chip **164** is shown schematically, the actual length, width, height and dimensions may vary depending on product requirements.

(21) At step **S06**, a second circuit layer module **170** is formed on the first circuit layer module **150** and the second chip **160**, as shown in FIG. 7. Specifically, the second circuit layer module **170** includes at least one the second dielectric layer **172** and at least one the second circuit layer **174**. The second dielectric layer **172** has a plurality of the second conductive vias **176**. The second circuit layer **174** is disposed on the second dielectric layer **172** and in contact with the second conductive vias **176**. The bottommost second circuit layer **174** is electrically connected to the second conductive pads **162** through the second conductive vias **176**. It is understood that the smallest layer number constituting the second circuit layer module **170** is one dielectric layer and one circuit layer. One skilled in the art can modify the layer number of the dielectric layer and the circuit layers based on actual needs.

(22) Details including materials and forming method of the second dielectric layer **172**, the second circuit layers **174** and the second conductive vias **176** are similar to those of the first dielectric layer **152**, the first circuit layers **154** and the first conductive vias **156** respectively, and therefore are not repeated herein. In addition, before the formation of the second circuit layers **174**, the abovementioned seed layer may be formed on the second dielectric layer **172**, and the details are not repeated herein.

(23) At step **S07**, a protecting layer **180** is formed on the second circuit layer module **170**, as shown in FIG. 8. The protecting layer **180** has a plurality of the openings **182**. A portion of the second circuit layer module **170** is exposed through the openings **182**. Specifically, as shown in FIG. 8, a portion of the outermost second circuit layers **174** of the second circuit layer module **170** is exposed through the openings **182**. In some embodiments, the protecting layer **180** may be made of soldering resist material or resins. Alternatively, the protecting layer **180** may be made of a material similar to that of the first dielectric layer **152** or the second dielectric layer **172**. The protecting layer **180** may be formed by a lamination process, a printing process, a coating process, or the like.

(24) Next, as shown in FIG. 9, the supporting layer **112**, the first release layer **114** and the second release layer **116** are removed from the structure shown in FIG. 8 to form two the package structure **100s**. In the conventional single-sided manufacturing method, warpage of the supporting layer is often encountered due to its structural asymmetry. However, in the embodiment, by simultaneously performing the same process on opposite surfaces of the supporting layer **112**, two symmetry package structures **100** are formed, such that warpage of two ends of the supporting layer **112** can be avoided. In addition, according to embodiments of the present disclosure, the overall reliability of the package structure is increased. The heat generated by the first chip **140** can be dissipated by the heat conduction of the metal layers **118** disposed on the bottom of the package structure **100**. In

addition, the heat generated by the second chip **160** can be dissipated by the heat conduction of the first circuit layers **154** disposed on the bottom of the second chip **160**, thereby increasing the stability of the second chip **160** when in use.

(25) Another aspect of the present disclosure is to provide a package structure. FIG. **9** illustrates a schematic cross-sectional view of a package structure **100** according to one embodiment of the present disclosure. The package structure **100** includes an insulating composite layer **120**, a sealant **130**, a first chip **140**, a circuit layer module **30**, a second chip **160** and a protecting layer **180**. In some embodiments, the insulating composite layer **120** includes a composite having an inorganic insulating material and an organic material. Details including material and forming method of the insulating composite layer **120** have been described above, and therefore are not repeated herein. The sealant **130** is located on the insulating composite layer **120**. The first chip **140** is embedded in the sealant **130**. The first chip **140** has a plurality of the first conductive pads **144** exposed through the sealant **130**. In some embodiments, the first chip **140** has a first surface **140a** and a second surface **140b** opposite thereto. The first conductive pads **144** are exposed through the first surface **140a**. The sealant **130** covers the second surface **140b**.

(26) The circuit layer module **30** is disposed on the sealant **130** and the first chip **140**. The circuit layer module **30** includes a plurality of circuit layers **320** and a plurality of dielectric layers **310**. Each dielectric layer has a plurality of conductive vias **330**. Each circuit layer **320** is disposed between adjacent dielectric layers **310** and in contact with the conductive vias **330**. The bottommost circuit layer **320** is electrically connected to the first conductive pads **144** through the conductive vias **330**. The second chip **160** has a plurality of second conductive pads **162** and is embedded in the circuit layer module **30**. The second conductive pads **162** are electrically connected to the circuit layers **320** through the conductive vias **330**. In one embodiment, the second chip **160** is disposed between the adjacent circuit layers **320** and the dielectric layers **310**, and is located on the circuit layers **320**. In another embodiment, the second chip **160** is disposed between the adjacent dielectric layers **310**. The protecting layer **180** is disposed on the circuit layer module **30**. The protecting layer **180** has a plurality of the openings **182** exposing a portion of the circuit layer module **30**.

(27) FIG. **10** illustrates a cross-sectional view of a package structure **200** according to another embodiment of the present disclosure. The package structure **200** includes an insulating composite layer **120**, a sealant **130**, a first chip **140**, a circuit layer module **30**, a second chip **160** and a protecting layer **180**. Compared to the package structure **100** shown in FIG. **9**, the package structure **200** shown in FIG. **10** does not have any metal layer **118**. The manufacturing method of the package structure **200** in the present embodiment is similar to that of the package structure **100**, except that in the present example, a metal layer **118** is removed (for example, by an etching process) after the formation of the package structure **100**. Consequently, there is no metal layer **118** in the package structure **200** shown in FIG. **10**.

(28) FIG. **11** illustrates a cross-sectional view of a package structure **300** according to another embodiment of the present disclosure. The package structure **300** includes a sealant **130**, a first chip **140**, a circuit layer module **30**, a second chip **160** and a protecting layer **180**. Compared to the package structure **200** shown in FIG. **10**, the package structure **300** shown in FIG. **11** does not have any insulating composite layer **120**. The manufacturing method of the package structure **300** in the present embodiment is similar to that of the package structure **200**, except that in the present example, an insulating composite layer **120** is removed (for example, by a polishing process) after the formation of the package structure **200**. Consequently, there is no insulating composite layer **120** in the package structure **300** shown in FIG. **11**.

(29) The present disclosure provides a method for manufacturing a package structure. The package structure manufactured by the method may have a higher reliability and integration density and thereby meets requirements of miniaturization and high processing speed. FIG. **12** is a schematic cross-sectional view showing another example of the package structure **400** of the present

disclosure. The manufacturing method of the package structure **400** is substantially similar to the manufacturing method of the package structure **100** shown in FIG. 2 through FIG. 9, except that the manufacturing method of the package structure **400** is performed on a single side of the carrier board **110** to form the package structure **400**. Specifically, the circuit layer module **30** of the package structure **400** includes the first circuit layer module **150** shown in FIG. 5 and the second circuit layer module **170** shown in FIG. 7. As shown in FIG. 12, the circuit layer module **30** includes a plurality of circuit layers **320** corresponding to the circuit layers **154** and **174** and a plurality of dielectric layers **310** corresponding to the dielectric layers **152** and **172**. Each dielectric layer **310** has a plurality of conductive vias **330** corresponding to the conductive vias **156** and **176**. The layer number, components, and materials of each layer and component in the single-sided fabrication have been described above, and therefore are not repeated herein.

(30) The insulating composite layer used in the package structure of the present disclosure can be regarded as a strengthening layer. The insulating composite layer has a higher elasticity modulus than that of a general dielectric layer or a packaging material. Therefore, the insulating composite layer can be used to increase the structural strength of the package structure of the present disclosure to prevent the carrier board from warpage, resulting in higher process yield and reliability of the package structure. The package structure also includes a second chip embedded in the circuit layer module, such that the integration density is increased and thereby meeting requirements of miniaturization and high processing speed.

(31) It will be apparent to those skilled in the art that various modifications and variations can be made to the structure of the present invention without departing from the scope or spirit of the invention. In view of the foregoing, it is intended that the present invention cover modifications and variations of this invention provided they fall within the scope of the following claims.

Claims

1. A method of manufacturing package structure, comprising steps of: providing a carrier board comprising a supporting layer, a first release layer, a second release layer and a plurality of metal layers, the first release layer and the second release layer are disposed on opposite surfaces of the supporting layer respectively, and the metal layers are disposed on the first release layer and the second release layer; forming an insulating composite layer on at least one of the metal layers; disposing a chip packaging module on at least one of the insulating composite layers, the chip packaging module comprising a sealant and a first chip embedded therein, wherein the first chip has a plurality of first conductive pads, the first conductive pads are exposed through the sealant; forming a first circuit layer module on the chip packaging module, wherein the first circuit layer module comprises at least one first dielectric layer and at least one first circuit layer, the first dielectric layer has a plurality of first conductive vias, the first circuit layer is located on the first dielectric layer, in contact with the first conductive vias, and electrically connected to the first conductive pads through the first conductive vias; disposing a second chip on at least one of the first circuit layer modules, the second chip having a plurality of second conductive pads; forming a second circuit layer module on at least one of the first circuit layer modules and the second chip, wherein the second circuit layer module comprises at least one second dielectric layer and at least one second circuit layers, the second dielectric layer having a plurality of second conductive vias, the second circuit layer is located on the second dielectric layer, in contact with the second conductive vias, and electrically connected to the second conductive pads through the second conductive vias; and forming a protecting layer on at least one of the second circuit layer modules, wherein the protecting layer has a plurality of openings exposing a portion of the second circuit layer module.

2. The method of claim 1, wherein the at least one first dielectric layer comprises a plurality of first dielectric layer, while the at least one first circuit layers comprises a plurality of first circuit layers.

3. The method of claim 2, wherein the step of disposing the second chip on at least one of the first circuit layer modules comprises disposing the second chip on an uppermost first circuit layers of the at least one first circuit layer of the first circuit layer module.
 4. The method of claim 3, wherein the step of disposing the second chip on at least one of the first circuit layer modules comprises disposing an adhesive layer between the uppermost first circuit layers and the second chip.
 5. The method of claim 2, further comprising disposing a third chip on an uppermost first dielectric layer of the at least one first dielectric layer of the first circuit layer module.
 6. The method of claim 1, wherein the first chip has a first surface and a second surface opposite to the first surface, the first conductive pads are exposed through the first surface, while the second surface is covered by the sealant.
 7. The method of claim 6, wherein each of the first conductive pads comprises a bottom portion below the first surface and at least one top portion over the first surface, and the top portion is in contact with the bottom portion.
 8. The method of claim 1, wherein the insulating composite layer comprises a composite having an inorganic insulating material and an organic material.
 9. The method of claim 1, wherein the protecting layer is made of a soldering resist material or resins.
 10. The method of claim 1, further comprising removing the supporting layer, the first release layer, and the second release layer to form two of the package structures.
-