

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12414458
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Yang; Lin et al.

Display panel and manufacturing method thereof

Abstract

Provided is a display panel, comprising a flexible substrate, a transition layer, a buffer layer, a drive layer, a functional layer, and a thin-film encapsulation layer. The transition layer covers one side of the flexible substrate; the buffer layer covers one side, away from a rigid carrier, of the transition layer; the drive layer covers one side, away from the transition layer, of the buffer layer; the functional layer covers one side, away from the buffer layer, of the drive layer; and the thin-film encapsulation layer covers the surface of the functional layer. According to the invention, a sulfydryl-containing transition layer is modified on a flexible substrate by means of sulfydryl modification to realize tight adhesion between the flexible substrate and a buffer layer in a drive layer, so that the adhesion force between the flexible substrate and the buffer layer is greatly enhanced by means of chemical adsorption.

Inventors:	Yang; Lin (Hubei, CN), Li; Xianjie (Hubei, CN), Luo; Jiajia (Hubei, CN), Huang; Jinchang (Hubei, CN)
Applicant:	Wuhan China Star Optoelectronics Semiconductor Display Technology Co., Ltd. (Hubei, CN)
Family ID:	66145894
Assignee:	Wuhan China Star Optoelectronics Semiconductor Display Technology Co., Ltd. (Wuhan, CN)
Appl. No.:	17/254879
Filed (or PCT Filed):	March 04, 2019
PCT No.:	PCT/CN2019/076829
PCT Pub. No.:	WO2020/133682
PCT Pub. Date:	July 02, 2020

Prior Publication Data

Document Identifier

US 20210273200 A1

Publication Date

Sep. 02, 2021

Foreign Application Priority Data

CN

201811579228.5

Dec. 24, 2018

Publication Classification

Int. Cl.: H10K77/10 (20230101); H10K50/844 (20230101); H10K59/80 (20230101); H10K71/00 (20230101); H10K59/12 (20230101)

U.S. Cl.:

CPC H10K77/111 (20230201); H10K50/844 (20230201); H10K59/873 (20230201); H10K71/00 (20230201); H10K59/12 (20230201); H10K59/1201 (20230201)

Field of Classification Search

CPC: H10K (50/844); H10K (59/12); H10K (71/00); H10K (77/111); H10K (59/1201); H10K (59/873); Y02E (10/549)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
6212057	12/2000	Kohara	361/306.3	H01G 4/08
2005/0145839	12/2004	Yamamoto	438/82	C08G 61/122
2006/0128826	12/2005	Ellison	522/127	C09D 181/02
2006/0132461	12/2005	Furukawa	345/173	H10K 71/80
2010/0013745	12/2009	Kim et al.	N/A	N/A
2011/0062603	12/2010	Hawker	257/E23.116	H10K 50/841
2012/0118478	12/2011	Park et al.	N/A	N/A
2014/0166995	12/2013	Lee et al.	N/A	N/A
2014/0175463	12/2013	Nam	438/28	H10K 59/126
2015/0303389	12/2014	Kim	156/60	H10K 77/111
2015/0314326	12/2014	Park et al.	N/A	N/A
2016/0197292	12/2015	Lee et al.	N/A	N/A
2016/0211350	12/2015	Koo	N/A	H01L 29/66757
2019/0067408	12/2018	Sun	N/A	G06V 10/147
2020/0142273	12/2019	Barile	N/A	C03C 4/14
2020/0273764	12/2019	Chen	N/A	C09D 5/00

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
102468452	12/2011	CN	N/A
103872069	12/2013	CN	N/A
103887322	12/2013	CN	N/A
104022123	12/2013	CN	N/A
104903947	12/2014	CN	N/A
105431893	12/2015	CN	N/A
103779390	12/2015	CN	N/A
108336143	12/2017	CN	N/A
108425104	12/2017	CN	N/A
108493198	12/2017	CN	N/A
WO 2020/133682	12/2019	WO	N/A

OTHER PUBLICATIONS

International Search Report and the Written Opinion Dated Sep. 24, 2019 From the International Searching Authority Re. Application No. PCT/CN2019/076829 and Its Translation of Search Report Into English. (9 Pages). cited by applicant

Primary Examiner: Abdelaziez; Yasser A

Background/Summary

RELATED APPLICATIONS

(1) This application is a National Phase of PCT Patent Application No. PCT/CN2019/076829 having International filing date of Mar. 4, 2019, which claims the benefit of priority of Chinese Patent Application No. 201811579228.5 filed on Dec. 24, 2018. The contents of the above applications are all incorporated by reference as if fully set forth herein in their entirety.

FIELD AND BACKGROUND OF THE INVENTION

(2) The present disclosure relates to a display panel and a manufacturing method thereof.

(3) At present, a flat panel display includes a liquid crystal display (LCD), a plasma display panel, an organic light emitting diode (OLED) display device, and the like. The OLED display device has the characteristics of low power consumption, high contrast ratio, wide viewing angle, lightness, flexibility, and the like. The OLED display devices with the large size and the small and medium size in the market become a kind of next-generation mainstream display technology.

(4) The OLED display device is an active light-emitting device, and the thickness of the OLED display device is less than 0.2 μm , such that ultrathin flexible display device can be realized by selecting the substrate with proper thickness and material, which is one of the important advantages of the OLED display device to distinguish from other kinds of display devices. However, a substrate used by an OLED display device on the market is a substrate of glass material. Since the flexible OLED display device still has some problems, the flexible OLED display device is particularly applied to display devices with the large size. An important reason of the application fields is the development of a flexible substrate that is stable and easy to peel off.

(5) A manufacturing method of the traditional flexible display device includes following steps. A flexible substrate is adhered to a hard layer by an adhesive, and a series of manufacturing steps is carried out on the flexible substrate to obtain a flexible display device. However, such a flexible substrate, e.g., polyacetamide, is easy to separate from a driving layer in the subsequent manufacturing process, thereby causing the problems and the product quality of the display

devices.

SUMMARY OF THE INVENTION

- (6) The present disclosure aims to provide a display panel that includes a flexible substrate, a transition layer, a buffer layer, a driving layer, a functional layer, and a thin film packaging layer. The transition layer covers a side of the flexible substrate. The buffer layer covers a side, away from the hard layer, of the transition layer. The driving layer covers a side, away from the transition layer, of the buffer layer. The functional layer covers a side, away from the buffer layer, of the driving layer. The thin film packaging layer covers surface of the functional layer.
- (7) In an embodiment, the transition layer comprises organic molecules having sulfydryl.
- (8) In an embodiment, material of the flexible substrate is selected from a group consisting of polyimide, diphenyl ether resin, and polyethylene naphthalate.
- (9) In an embodiment, the buffer layer comprises titanium dioxide or silicon dioxide.
- (10) In an embodiment, the thickness of the buffer layer ranges from 0.5 to 500 microns.
- (11) In another embodiment, the present disclosure aims to provide a manufacturing method of a display panel, comprising steps of: coating a layer of organic polymer on a upper surface of a hard layer, wherein the organic polymer is dried to form a flexible substrate; placing a flexible substrate in a sulfydryl-containing organic solution, wherein after the flexible substrate is taken out, the organic solution is dried to form a transition layer; forming a buffer layer on a upper surface of the transition layer; forming a driving layer on a upper surface of the buffer layer; forming a functional layer on a upper surface of the driving layer; and coating a thin film packaging layer on a upper surface of the functional layer.
- (12) In an embodiment, the step of placing the flexible substrate in the sulfydryl-containing organic solution comprises: time for placing the flexible substrate in the organic solution is 5 to 30 minutes; temperature of the organic solution is 20 to 50 degrees Celsius; pH value of the organic solution is 2 to 8; and time for drying the organic solution is 15 to 30 minutes.
- (13) In an embodiment, the organic solution is selected from a group consisting of 2-mercaptopropionic acid, mercaptopropionic acid, and 3-mercaptopbutyric acid.
- (14) In an embodiment, the driving layer is selected from a group consisting of a low-temperature polycrystalline silicon thin film transistor, a thin film transistor, and an oxide thin film transistor.
- (15) In an embodiment, the step of coating the thin film packaging layer on the upper surface of the functional layer comprises a chemical vaporization deposition method, an atomic layer deposition method, or an ink-jet printing method.
- (16) The present disclosure provides a chemical adjustment method. A sulfydryl-containing transition layer **102** is modified on the flexible substrate by using a sulfydryl-modified method, and is used for tightly adhering the flexible substrate and the buffer layers **103** of the driving layer **104**. The adhesive force between the flexible substrate and the buffer layer **103** is greatly enhanced by chemical adsorption, such that the phenomenon separating the flexible substrate from the driving layer **104** in the process of vaporization of the substrate or during a later use process can be effectively avoided, and the product quality and the yield rate are improved.

Description

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

- (1) The following embodiments refer to the accompanying drawings for exemplifying specific implementable embodiments of the present disclosure in a suitable computing environment. It should be noted that the exemplary described embodiments are configured to describe and understand the present disclosure, but the present disclosure is not limited thereto.
- (2) FIG. 1 is a schematic structural diagram of a display panel according to an embodiment of the present disclosure.

(3) FIG. 2 is a flowchart of a manufacturing method of a display panel according to an embodiment of the present disclosure.

(4) FIG. 3 is a schematic structural diagram of a flexible substrate and a transition layer according to an embodiment of the present disclosure.

(5) FIG. 4 is a schematic structural diagram of a flexible substrate, a transition layer, and a buffer layer according to an embodiment of the present disclosure.

(6) FIG. 5 is a schematic structural diagram of a flexible substrate, a transition layer, a buffer layer, and a driving layer according to an embodiment of the present disclosure.

(7) FIG. 6 is a schematic cross-sectional diagram of a flexible substrate, a transition layer, a buffer layer, a driving layer, and a functional layer according to an embodiment of the present disclosure.

DESCRIPTION OF SPECIFIC EMBODIMENTS OF THE INVENTION

(8) Directional terms, such as an upper side, a lower side, a front side, a back side, a left side, a right side, an inner side, an outer side, and a lateral side, mentioned in the present disclosure are only for reference. Therefore, the directional terms are used for describing and understanding rather than limiting the present disclosure. In the figures, units having similar structures are used for the same reference numbers.

(9) Embodiments of the present disclosure will be described in detail with reference to the accompanying drawings. The present disclosure can be embodied in many different forms and should not be construed as limited to the specific embodiments set forth herein. The embodiment of the present disclosure is used for explaining the practical application of the disclosure, so that other technicians in the art can understand various embodiments of the present disclosure and various modification schemes suitable for specific expected applications.

(10) As shown in FIG. 1, the present disclosure provides a display panel **100** including a flexible substrate **101**, a transition layer **102**, a buffer layer **103**, a driving layer **104**, a functional layer **105**, and a thin film packaging layer **106**.

(11) The material of the flexible substrate **101** includes, but is not limited to, polyimide, diphenyl ether resin, or polyethylene naphthalate.

(12) The transition layer **102** is configured to cover a side of a hard plate, and the transition layer **102** is an organic molecule containing sulfydryl. The transition layer **102** is formed by reacting an organic solution with the organic polymer on the flexible substrate **101**. The organic solution includes, but not limited to, 2-mercaptopropionic acid, mercaptopropionic acid, or 3-mercaptopropionic acid, where the chemical modification speed and uniformity can be controlled through the temperature and the pH value, such that the adhesive force of the transition layer **102** and the flexible substrate **101** can be increased.

(13) The buffer layer **103** is configured to cover a side, away from a hard layer, of the transition layer **102**, and the buffer layer **103** is formed on the surface of the transition layer **102** by a chemical vaporization deposition (CVD) method or an atomic layer deposition (ALD) method. In an embodiment, the buffer layer **103** is made of TiO_2 , SiO_2 , and the thickness of the buffer layer **103** ranges from 0.5 μm to 500 μm . In other embodiments, the thickness of the buffer layer **103** can be 10 μm , 50 μm , 100 μm , 250 nm or 400 nm, and is preferably 100 nm.

(14) The driving layer **104** is configured to cover a side, away from the transition layer **102**, of the buffer layer **103**. The driving layer **104** is a low-temperature polycrystalline silicon thin film transistor (LTPS-TFT), a thin film transistor (TFT), or an oxide thin film transistor. In an embodiment, the driving layer **104** is used to drive a panel to display.

(15) The functional layer **105** is configured to cover a side, away from the buffer layer **103**, of the driving layer **104**. The functional layer **105** can be an OLED display device including an anode, a hole injection layer, a hole transmission layer, a light-emitting electron transmission layer, an electron injection layer, and a cathode. The anode is coated on a side, away from the buffer layer **103**, of the driving layer **104**. The hole injection layer is configured to a side, away from the driving layer **104**, of the anode. The hole transport layer is configured to cover a side, away from

the anode side, of the hole injection layer. The light-emitting layer is configured to cover a side, away from the hole injection layer, of the hole transport layer. The electron transmission layer is configured to cover a side, away from the hole transmission layer, of the light-emitting layer. The electron injection layer is configured to cover a side, away from the light-emitting layer, of the electron transmission layer. The cathode is coated on a side, away from the electron transmission layer, of the electron injection layer. In other embodiments, the functional layer **105** can also be a liquid crystal display structure of an LCD, such that the imaging effect of the pixels of the display panel is achieved.

(16) The thin film packaging layer **106** is configured to cover the surface of the functional layer **105**. The manufacturing method of the thin film packaging layer **106** can be a chemical vaporization deposition method, an atomic layer deposition method or an ink-jet printing method, and the method is preferably a chemical vaporization deposition method. The thin film packaging layer mainly plays roles of isolating water and oxygen and can be used for protecting related devices of the functional layer **105**.

(17) As shown in FIG. 2, the present disclosure further provides a manufacturing method of the display panel **100**, including the following steps **S1** to **S6**.

(18) At step **S1**, as shown in FIG. 3, an organic polymer is coated on the upper surface of the hard layer, and the organic polymer is dried to form a flexible substrate **101**. The hard layer is glass or hard resin, and the organic polymer is selected from a group consisting of polyimide, diphenyl ether resin, and polyethylene naphthalate.

(19) At step **S2**, the flexible substrate **101** is placed in a sulfhydryl-containing organic solution, and after the flexible substrate **101** is taken out, the organic solution is dried to form a transition layer **102** on the flexible substrate **101**. The flexible substrate **101** is placed for 5 to 30 minutes, preferably 20 minutes. In other embodiments, the time for placing the flexible substrate **101** can also be 10 minutes, 15 minutes, or 25 minutes. The time for placing the flexible substrate **101** in the organic solution is from 20 to 50 degrees Celsius and preferably 30 degrees Celsius, and can also be 25 degrees Celsius or 40 degrees Celsius in other embodiments, where the pH value of the organic solution is from 2 to 8, preferably, the pH value is 5, and the pH value can be 3, 4, or 6 in other embodiments. The drying time of the organic solution is from 15 to 30 minutes, preferably 25 minutes, and can also be 20 minutes, 24 minutes or 28 minutes in other embodiments.

(20) The transition layer **102** is manufactured by reacting an organic solution with the organic polymer of the flexible substrate **101** to form the transition layer **102**.

(21) The organic solution includes, but not limited to, 2-mercaptopropionic acid, mercaptopropionic acid, or 3-mercaptopropionic acid, where the chemical modification speed and uniformity can be controlled through the temperature and the pH value, such that the adhesive force of the transition layer **102** and the flexible substrate **101** can be increased.

(22) At step **S3**, as shown in FIG. 4, a buffer layer **103** is formed on the upper surface of the transition layer **102**, and the buffer layer **103** is formed on the surface of the transition layer **102** by a chemical vaporization deposition (CVD) method or an atomic layer deposition (ALD) method. In an embodiment, the buffer layer **103** is made of TiO_2 , SiO_2 , and the thickness of the buffer layer **103** ranges from 0.5 μm to 500 μm . In other embodiments, the thickness of the buffer layer **103** can be 10 μm , 50 μm , 100 μm , 250 nm or 400 nm, and is preferably 100 nm.

(23) At step **S4**, as shown in FIG. 5, a driving layer **104** is formed on the upper surface of the buffer layer **103**. The driving layer **104** is a low-temperature polycrystalline silicon thin film transistor (LTPS-TFT), a thin film transistor (TFT), or an oxide thin film transistor. In an embodiment, the driving layer **104** is used to drive a panel to display.

(24) At step **S5**, as shown in FIG. 6, a functional layer **105** is formed on a upper surface of the driving layer **104**. The functional layer **105** can be an OLED display device including an anode, a hole injection layer, a hole transmission layer, a light-emitting electron transmission layer, an electron injection layer, and a cathode. The anode is coated on a side, away from the buffer layer

103, of the driving layer **104**. The hole injection layer is configured to a side, away from the driving layer **104**, of the anode. The hole transport layer is configured to cover a side, away from the anode side, of the hole injection layer. The light-emitting layer is configured to cover a side, away from the hole injection layer, of the hole transport layer. The electron transmission layer is configured to cover a side, away from the hole transmission layer, of the light-emitting layer. The electron injection layer is configured to cover a side, away from the light-emitting layer, of the electron transmission layer. The cathode is coated on a side, away from the electron transmission layer, of the electron injection layer. In other embodiments, the functional layer **105** can also be a liquid crystal display structure of an LCD, such that the imaging effect of the pixels of the display panel is achieved.

(25) At step **S6**, a thin film packaging layer **106** is coated on the upper surface of the functional layer **105**. The manufacturing method of the thin film packaging layer **106** can be a chemical vaporization deposition method, an atomic layer deposition method or an ink-jet printing method, and the method is preferably a chemical vaporization deposition method. The thin film packaging layer mainly plays roles of isolating water and oxygen and can be used for protecting related devices of the functional layer **105**.

(26) The present disclosure provides a chemical adjustment method. A sulfydryl-containing transition layer **102** is modified on the flexible substrate by using a sulfydryl-modified method, and is used for tightly adhering the flexible substrate and the buffer layers **103** of the driving layer **104**. The adhesive force between the flexible substrate and the buffer layer **103** is greatly enhanced by chemical adsorption, such that the phenomenon separating the flexible substrate from the driving layer **104** in the process of vaporization of the substrate or during a later use process can be effectively avoided, and the product quality and the yield rate are improved.

(27) As is understood by a person skilled in the art, the foregoing preferred embodiments of the present disclosure are illustrative rather than limiting of the present disclosure. It is intended that they cover various modifications and similar arrangements be included within the spirit and scope of the present disclosure, the scope of which should be accorded the broadest interpretation so as to encompass all such modifications and similar structures.

Claims

1. A manufacturing method of a display panel, comprising steps of: coating a layer of organic polymer on an upper surface of a hard layer, wherein the organic polymer is dried to form a flexible substrate; placing a flexible substrate in a sulfydryl-containing organic solution, wherein after the flexible substrate is taken out, the organic solution is dried to form a transition layer to be in direct contact with the flexible substrate; forming a buffer layer on an upper surface of the transition layer, wherein the buffer layer is in direct contact with the upper surface of the transition layer; forming a driving layer on an upper surface of the buffer layer; forming a functional layer on an upper surface of the driving layer; and coating a thin film packaging layer on an upper surface of the functional layer, wherein the organic solution is selected from a group consisting of 2-mercaptopropionic acid, mercaptopropionic acid, and 3-mercaptopropionic acid, and the buffer layer comprises titanium dioxide or silicon dioxide, and wherein material of the flexible substrate is selected from a group consisting of polyimide, diphenyl ether resin, and polyethylene naphthalate.
2. The display panel manufacturing method according to claim 1, wherein the step of placing the flexible substrate in the sulfydryl-containing organic solution comprises: time for placing the flexible substrate in the organic solution is 5 to 30 minutes; temperature of the organic solution is 20 to 50 degrees Celsius; pH value of the organic solution is 2 to 8; and time for drying the organic solution is 15 to 30 minutes.
3. The display panel manufacturing method according to claim 1, wherein the driving layer is selected from a group consisting of a low-temperature polycrystalline silicon thin film transistor, a

thin film transistor, and an oxide thin film transistor.

4. The display panel manufacturing method according to claim 1, wherein the step of coating the thin film packaging layer on the upper surface of the functional layer comprises a chemical vaporization deposition method, an atomic layer deposition method, or an ink-jet printing method.
 5. The display panel manufacturing method according to claim 1, wherein the hard layer is glass or hard resin.
 6. The display panel manufacturing method according to claim 1, wherein the organic polymer is selected from a group consisting of polyimide, diphenyl ether resin, and polyethylene naphthalate.
 7. The display panel manufacturing method according to claim 1, wherein the forming of the buffer layer on the upper surface of the transition layer comprises: forming the buffer layer on the upper surface of the transition layer by a chemical vaporization deposition (CVD) method or an atomic layer deposition (ALD) method.
 8. The display panel manufacturing method according to claim 1, wherein the buffer layer is made of at least one of TiO_2 and SiO_2 .
 9. The display panel manufacturing method according to claim 1, wherein a thickness of the buffer layer ranges from 0.5 μm to 500 μm .
 10. The display panel manufacturing method according to claim 9, wherein the thickness of the buffer layer is 10 μm , 50 μm , 100 μm , 250 μm or 400 μm .
 11. The display panel manufacturing method according to claim 1, wherein the functional layer can be an OLED display device including an anode, a hole injection layer, a hole transmission layer, a light-emitting electron transmission layer, an electron injection layer, and a cathode.
 12. The display panel manufacturing method according to claim 2, wherein the time for placing the flexible substrate in the organic solution is 10 minutes, 15 minutes, or 25 minutes.
 13. The display panel manufacturing method according to claim 2, wherein the temperature of the organic solution is 25 degrees Celsius, 30 degrees Celsius, or 40 degrees Celsius.
 14. The display panel manufacturing method according to claim 2, wherein the pH value of the organic solution is 3, 4, 5, or 6.
 15. The display panel manufacturing method according to claim 2, wherein the time for drying the organic solution is 20 minutes, 24 minutes, 25 minutes, or 28 minutes.
-