

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250280584

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

CHIANG; Hsu

SEMICONDUCTOR MEMORY DEVICE MANUFACTURING METHOD

Abstract

A semiconductor memory device manufacturing method includes the following steps. A gate structure is formed on a substrate. First gate nitride spacers are formed around the gate structure. A gate oxide material is formed between adjacent first gate nitride spacers. A first gate cap nitride layer is formed. The first gate cap nitride layer is patterned and used as a hard mask to etch gate contact trenches. Second gate nitride spacers are formed in the gate contact trenches. A gate contact oxide material is formed in the gate contact trenches. A second gate cap nitride layer is formed. The second gate cap nitride layer is patterned to form an opening to expose the gate contact oxide material. The gate contact oxide material is removed from the gate contact trenches. A gate contact metal material is formed into the gate contact trenches.

Inventors: CHIANG; Hsu (New Taipei City, TW)

Applicant: NANYA TECHNOLOGY CORPORATION (New Taipei city, TW)

Family ID: 96856745

Appl. No.: 18/593865

Filed: March 02, 2024

Publication Classification

Int. Cl.: H01L21/28 (20250101); H01L29/66 (20060101)

U.S. Cl.:

CPC H10D64/035 (20250101); H10D30/0411 (20250101);

Background/Summary

BACKGROUND

Field of Disclosure

[0001] The present disclosure relates to a semiconductor memory device manufacturing method.

Description of Related Art

[0002] An integrated circuit (IC) device (also referred to as a semiconductor chip) can contain millions of transistors and other circuit elements that are fabricated on a single silicon crystal substrate (wafer). In a semiconductor memory device, a gate structure is a crucial component responsible for controlling the flow of electrical current between the source and drain terminals of the transistor. For example, in a NAND flash memory cell, the gate structure plays a crucial role in storing and retrieving data. By applying specific voltages to the gate, electrons can be trapped or released in the floating gate, altering the cell's electrical characteristics and storing binary data. This manipulation of charge within the gate structure enables the memory device to retain information even when power is removed.

SUMMARY

[0003] The present disclosure provides semiconductor memory devices and manufacturing methods thereof to deal with the needs of the prior art problems.

[0004] In one or more embodiments, a semiconductor memory device manufacturing method including: forming a gate structure on a substrate, wherein the gate structure comprises a gate conductive portion and a gate oxide layer; forming first gate nitride spacers around the gate structure; forming a gate oxide material between adjacent ones of the first gate nitride spacers; forming a first gate cap nitride layer over the gate structure, the first gate nitride spacers and the gate oxide material; patterning the first gate cap nitride layer and using the patterned first gate cap nitride layer as a hard mask to etch gate contact trenches in the gate oxide material, wherein each gate contact trench exposes a corresponding gate source/drain region in the substrate; forming second gate nitride spacers in the gate contact trenches; forming a gate contact oxide material in the gate contact trenches and over the second gate nitride spacers; forming a second gate cap nitride layer over the gate structure, the first and second gate nitride spacers and the gate contact oxide material; patterning the second gate cap nitride layer to form an opening to expose the gate contact oxide material; removing the gate contact oxide material from the gate contact trenches; and forming a gate contact metal material into the gate contact trenches.

[0005] In one or more embodiments, the gate conductive portion includes a polysilicon portion and a tungsten portion on a top of the polysilicon portion.

[0006] In one or more embodiments, the gate contact metal material is tungsten.

[0007] In one or more embodiments, the method further includes: performing a chemical mechanical polishing process to remove excess gate oxide material.

[0008] In one or more embodiments, the method further includes: performing a chemical mechanical polishing process to remove excess gate contact oxide material.

[0009] In one or more embodiments, the method further includes: performing a chemical mechanical polishing process to remove excess gate contact metal material.

[0010] In one or more embodiments, an inner sidewall of each gate contact trench is perpendicular to the corresponding gate source/drain region.

[0011] In one or more embodiments, the method further includes: performing a source/drain implant process to the corresponding gate source/drain region.

[0012] In one or more embodiments, the second gate nitride spacers are formed by an atomic layer deposition process.

[0013] In one or more embodiments, a semiconductor memory device manufacturing method including: forming a gate structure on a substrate; forming first gate nitride spacers around the gate structure; forming a gate oxide material between adjacent ones of the first gate nitride spacers; forming a first gate cap nitride layer over the gate structure, the first gate nitride spacers and the

gate oxide material; patterning the first gate cap nitride layer and using the patterned first gate cap nitride layer as a hard mask to etch gate contact trenches in the gate oxide material, wherein each gate contact trench has a first opening having a first width; forming second gate nitride spacers in the gate contact trenches; forming a gate contact oxide material in the gate contact trenches and over the second gate nitride spacers; forming a second gate cap nitride layer over the gate structure, the first and second gate nitride spacers and the gate contact oxide material; patterning the second gate cap nitride layer to form a second opening to expose the gate contact oxide material, wherein the second opening has a second width greater than the first width; removing the gate contact oxide material from the gate contact trenches; and forming a gate contact metal material into the gate contact trenches to form a gate contact.

[0014] In one or more embodiments, the gate structure includes a gate conductive portion and a gate oxide layer, the gate conductive portion includes a polysilicon portion and a tungsten portion on a top of the polysilicon portion.

[0015] In one or more embodiments, the gate contact metal material is tungsten.

[0016] In one or more embodiments, the method further includes: performing a chemical mechanical polishing process to remove excess gate oxide material.

[0017] In one or more embodiments, the method further includes: performing a chemical mechanical polishing process to remove excess gate contact oxide material.

[0018] In one or more embodiments, the method further includes: performing a chemical mechanical polishing process to remove excess gate contact metal material.

[0019] In one or more embodiments, each gate contact includes a T-shaped profile.

[0020] In one or more embodiments, the second gate nitride spacers are formed by an atomic layer deposition process.

[0021] In one or more embodiments, each gate contact trench exposes a corresponding gate source/drain region in the substrate.

[0022] In one or more embodiments, the method further includes: performing a source/drain implant process to the corresponding gate source/drain region.

[0023] In one or more embodiments, each second gate nitride spacer has a uniform thickness and extends in a lengthwise direction perpendicular to the corresponding gate source/drain region.

[0024] In sum, the semiconductor memory device manufacturing method disclosed herein utilizes the process steps to form vertical gate oxide spacers, thereby forming a uniform distance between the gate structure and the gate contact, and the gate contact is equipped with a wider bottom in contact with the gate source/drain region.

[0025] It is to be understood that both the foregoing general description and the following detailed description are by examples, and are intended to provide further explanation of the disclosure as claimed.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0026] The disclosure can be more fully understood by reading the following detailed description of the embodiment, with reference made to the accompanying drawings as follows:

[0027] FIGS. 1-5 illustrate cross-sectional views of several steps of a semiconductor memory manufacturing process according to some embodiments of the present disclosure; and

[0028] FIG. 6 illustrates a flowchart of several steps of a semiconductor memory manufacturing process according to some embodiments of the present disclosure.

DETAILED DESCRIPTION

[0029] Reference will now be made in detail to the present embodiments of the disclosure, examples of which are illustrated in the accompanying drawings. Wherever possible, the same

reference numbers are used in the drawings and the description to refer to the same or like parts. [0030] Reference is made to FIGS. **1-6**, FIGS. **1-5** illustrate cross-sectional views of several steps of a semiconductor memory manufacturing process according to some embodiments of the present disclosure, and FIG. **6** illustrates a flowchart of several steps of a semiconductor memory manufacturing process **200** according to some embodiments of the present disclosure. The cross-sectional view illustrates a portion of a memory device **100** including gate structures **102**. A semiconductor substrate **101** is processed to form active areas. Several steps are typically involved in semiconductor processing. A suitable semiconductor substrate, such as silicon (Si), is chosen based on the desired device specifications and requirements. A thin layer of silicon dioxide (SiO₂) may be on the surface of the substrate. This can be achieved through thermal oxidation, where the substrate is exposed to an oxygen-rich environment at high temperatures, or by using deposition techniques such as chemical vapor deposition (CVD) or plasma-enhanced chemical vapor deposition (PECVD). A layer of photosensitive material, known as photoresist, is coated onto the oxide layer. Then, expose the photoresist to ultraviolet (UV) light through a photomask containing the desired pattern. This step transfers the pattern onto the photoresist. The exposed photoresist is developed using a suitable developer solution. This selectively removes either the exposed (positive photoresist) or unexposed (negative photoresist) regions of the photoresist, leaving behind the desired pattern. An etching process, such as plasma etching or wet etching, is used to selectively remove the exposed oxide layer where the active area will be formed. The patterned photoresist acts as a mask, protecting the regions where the oxide is desired. Ion implantation is performed to introduce p-type or n-type dopant atoms into the exposed semiconductor substrate regions where the active devices will be formed. The dopants modify the electrical properties of the substrate, creating regions with desired conductivity characteristics. The implanted dopants are activated and crystal lattice damage caused by the implantation process is repaired through an annealing process. This step typically involves subjecting the substrate to high temperatures for a specific duration.

[0031] In step **202** of the process **200** (referring to FIG. **1**), a gate structure **102** can be formed on a substrate **101**. In one or more embodiments, to form gate structures **102** on a substrate **101** may include following steps. A clean substrate **101**, typically made of silicon, can be prepared. A thin gate oxide layer **102a** may be applied on the substrate **101** to act as an insulating layer. A layer of polysilicon portion **102b** can be deposited on top of the gate oxide layer **102a**. This layer serves as the foundation for the gate conductive portion. A layer of tungsten portion **102c** can be deposited on the polysilicon portion **102b**. This is usually done through a process like chemical vapor deposition (CVD). Photolithography techniques are utilized to selectively expose and develop the polysilicon and tungsten layers, forming the desired gate structure pattern. The exposed areas of the polysilicon and tungsten layers are etched away, thereby leaving behind the gate structures according to the pattern. A thorough cleaning step may be performed to remove any residues and contaminants from the substrate surface. An annealing process may be optionally performed to improve the structural integrity and electrical properties of the gate structures **102**.

[0032] In step **204** of the process **200** (referring to FIG. **1**), first gate nitride spacers **104** can be formed around the gate structure **102**. In one or more embodiments, a layer of nitride material can be deposited on the entire substrate **101**, covering the gate structures **102** and the surrounding area. An anisotropic etching process, such as reactive ion etching (RIE), may be utilized to selectively remove the nitride material from the horizontal surfaces, leaving the nitride material only on the vertical or lateral sidewalls of the gate structure **102**.

[0033] In step **206** of the process **200** (referring to FIG. **2**), a gate oxide material **108** can be formed in void spaces **105** between adjacent first gate nitride spacers **104**. In one or more embodiments, the gate oxide material **108** can be fully filled into the void spaces **105** between adjacent first gate nitride spacers **104**. The gate oxide material **108** can be filled through techniques like chemical vapor deposition (CVD). A chemical mechanical polishing process may be performed to remove

excess gate oxide material **108** and create a smooth and even surface.

[0034] In step **208** of the process **200** (referring to FIG. 2), a first gate cap nitride layer **106** can be formed over the gate structure **102**, the first gate nitride spacers **104** and the gate oxide material **108**. In one or more embodiments, a layer of nitride material can be deposited over the entire substrate, covering the gate structure **102**, first gate nitride spacers **104**, and gate oxide material **108**. This can be done using techniques like chemical vapor deposition (CVD) or physical vapor deposition (PVD).

[0035] In step **210** of the process **200** (referring to FIG. 3), the first gate cap nitride layer **106** can be patterned and used as a hard mask to etch gate contact trenches **107** in the gate oxide material **108**. In one or more embodiments, a photoresist layer may be applied on top of the first gate cap nitride layer **106**, and the photoresist layer is exposed to UV light through a photomask containing a desired pattern for gate contact trenches **107**. The photoresist layer is then developed to create openings corresponding to the desired trench pattern. An anisotropic etching process (e.g., reactive ion etching or plasma etching) can be utilized to selectively remove the exposed areas of the first gate cap nitride layer **106**. This leaves behind the patterned first gate cap nitride layer **106** as a hard mask. An etching process is performed using the patterned first gate cap nitride layer **106** as a hard mask to etch gate contact trenches **107** into the gate oxide material **108** until each gate contact trench **107** exposes a corresponding gate source/drain region **103** in the substrate **101**.

[0036] In one or more embodiments, an inner sidewall (**107a**, **107b**) of each gate contact trench **107** is perpendicular to a top surface of the corresponding gate source/drain region **103**. In one or more embodiments, a source/drain implant process **113** can be performed to the corresponding gate source/drain region **103** to alter doping concentrations in the source and drain areas adjacent to the gate structure. With vertical sidewall (**107a**, **107b**) of each gate contact trench **107**, the gate source/drain region **103** can be defined with a broad area.

[0037] In step **212** of the process **200** (referring to FIG. 4), second gate nitride spacers **110** can be formed in the gate contact trenches **107** to be in contact with lateral sidewalls (**107a**, **107b**) of the remaining gate oxide material (**108a**, **108b**) that is not etched away. In one or more embodiments, the second gate nitride spacers **110** can be deposited using an atomic layer deposition process to provide a conformal coating, ensuring uniform coverage on the lateral sidewalls (**107a**, **107b**) of the remaining gate oxide material (**108a**, **108b**) in the gate contact trenches **107**. An etch-back process may be optionally performed to remove excess material from the top surface, leaving the nitride spacers primarily on the sidewalls. In one or more embodiments, each second gate nitride spacer **110** has a uniform thickness and extends in a lengthwise direction perpendicular to the corresponding gate source/drain region **103**.

[0038] In step **214** of the process **200** (referring to FIG. 4), a gate contact oxide material **109** can be formed in the gate contact trenches **107** and over the second gate nitride spacers **110**. In one or more embodiments, a deposition technique like Chemical Vapor Deposition (CVD) or Atomic Layer Deposition (ALD) can be utilized to deposit the gate contact oxide material **109**. A CMP process may be performed to planarize the surface, removing excess oxide material and ensuring a smooth, even surface.

[0039] In step **216** of the process **200** (referring to FIG. 4), a second gate cap nitride layer **112** can be formed over the gate structure **102**, the first and second gate nitride spacers (**104**, **110**), the first gate cap nitride layer **106** and the gate contact oxide material **109**. In one or more embodiments, a layer of nitride material can be deposited over the entire substrate, covering the gate structure **102**, the first and second gate nitride spacers (**104**, **110**), the remaining gate oxide material (**108a**, **108b**) and the gate contact oxide material **109**. This can be done using techniques like chemical vapor deposition (CVD) or physical vapor deposition (PVD).

[0040] In step **218** of the process **200** (referring to FIG. 5), the second gate cap nitride layer **112** can be patterned to form an opening **115** to expose the gate contact oxide material **109**. In one or more embodiments, a photoresist layer may be applied on top of the second gate cap nitride layer

112, and the photoresist layer is exposed to UV light through a photomask containing a desired pattern for the opening **115**. The photoresist layer is then developed to create openings corresponding to the desired trench pattern. An anisotropic etching process (e.g., reactive ion etching or plasma etching) can be utilized to selectively remove the exposed areas of the second gate cap nitride layer **112** until the gate contact oxide material **109** is exposed. In one or more embodiments, the opening **115** has a width W_2 greater than a width W_1 of the gate contact trench **107**. After step **218**, a gate spacer stack, including the second gate nitride spacer **110**, the remaining gate oxide material (**108a** or **108b**) and the first gate nitride spacer **104**, is formed on sidewalls of the gate structure **102** with a uniform thickness (e.g., a uniform distance D).

[0041] In step **220** of the process **200** (referring to FIG. 5), the gate contact oxide material **109** can be removed from the gate contact trenches **107**. In one or more embodiments, a wet etching can be used to remove the gate contact oxide material **109** from the gate contact trenches **107**.

[0042] In step **222** of the process **200** (referring to FIG. 5), a gate contact metal material can be filled into the gate contact trench **107** and the opening **115** to form a gate contact **116**. In one or more embodiments, each gate contact **116** comprises a T-shaped profile. In one or more embodiments, the gate contact metal material is tungsten or tungsten-based material. Since the gate spacer stack has a uniform thickness, a distance D between the gate structure **102** and the gate contact **116** is maintained substantially the same from the tungsten portion **102c** to the gate oxide layer **102a**, and the gate contact **116** has a wider bottom in contact with the gate source/drain region **103**.

[0043] In sum, the semiconductor memory device manufacturing method disclosed herein utilizes the process steps to form vertical gate oxide spacers, thereby forming a uniform distance between the gate structure and the gate contact, and the gate contact is equipped with a wider bottom in contact with the gate source/drain region.

[0044] Although the present disclosure has been described in considerable detail with reference to certain embodiments thereof, other embodiments are possible. Therefore, the spirit and scope of the appended claims should not be limited to the description of the embodiments contained herein.

[0045] It will be apparent to those skilled in the art that various modifications and variations can be made to the structure of the present disclosure without departing from the scope or spirit of the disclosure. In view of the foregoing, it is intended that the present disclosure cover modifications and variations of this disclosure provided they fall within the scope of the following claims.

Claims

1. A semiconductor memory device manufacturing method comprising: forming a gate structure on a substrate, wherein the gate structure comprises a gate conductive portion and a gate oxide layer; forming first gate nitride spacers around the gate structure; forming a gate oxide material between adjacent ones of the first gate nitride spacers; forming a first gate cap nitride layer over the gate structure, the first gate nitride spacers and the gate oxide material; patterning the first gate cap nitride layer and using the patterned first gate cap nitride layer as a hard mask to etch gate contact trenches in the gate oxide material, wherein each gate contact trench exposes a corresponding gate source/drain region in the substrate; forming second gate nitride spacers in the gate contact trenches; forming a gate contact oxide material in the gate contact trenches and over the second gate nitride spacers; forming a second gate cap nitride layer over the gate structure, the first and second gate nitride spacers and the gate contact oxide material; patterning the second gate cap nitride layer to form an opening to expose the gate contact oxide material; removing the gate contact oxide material from the gate contact trenches; and forming a gate contact metal material into the gate contact trenches.

2. The method of claim 1, wherein the gate conductive portion comprises a polysilicon portion and a tungsten portion on a top of the polysilicon portion.

3. The method of claim 1, wherein the gate contact metal material comprises tungsten.
 4. The method of claim 1 further comprising: performing a chemical mechanical polishing process to remove excess gate oxide material.
 5. The method of claim 1 further comprising: performing a chemical mechanical polishing process to remove excess gate contact oxide material.
 6. The method of claim 1 further comprising: performing a chemical mechanical polishing process to remove excess gate contact metal material.
 7. The method of claim 1, wherein an inner sidewall of each gate contact trench is perpendicular to the corresponding gate source/drain region.
 8. The method of claim 1 further comprising: performing a source/drain implant process to the corresponding gate source/drain region.
 9. The method of claim 1, wherein the second gate nitride spacers are formed by an atomic layer deposition process.
 10. A semiconductor memory device manufacturing method comprising: forming a gate structure on a substrate; forming first gate nitride spacers around the gate structure; forming a gate oxide material between adjacent ones of the first gate nitride spacers; forming a first gate cap nitride layer over the gate structure, the first gate nitride spacers and the gate oxide material; patterning the first gate cap nitride layer and using the patterned first gate cap nitride layer as a hard mask to etch gate contact trenches in the gate oxide material, wherein each gate contact trench has a first opening having a first width; forming second gate nitride spacers in the gate contact trenches; forming a gate contact oxide material in the gate contact trenches and over the second gate nitride spacers; forming a second gate cap nitride layer over the gate structure, the first and second gate nitride spacers and the gate contact oxide material; patterning the second gate cap nitride layer to form a second opening to expose the gate contact oxide material, wherein the second opening has a second width greater than the first width; removing the gate contact oxide material from the gate contact trenches; and forming a gate contact metal material into the gate contact trenches to form gate contacts.
 11. The method of claim 10, wherein the gate structure comprises a gate conductive portion and a gate oxide layer, the gate conductive portion comprises a polysilicon portion and a tungsten portion on a top of the polysilicon portion.
 12. The method of claim 10, wherein the gate contact metal material comprises tungsten.
 13. The method of claim 10 further comprising: performing a chemical mechanical polishing process to remove excess gate oxide material.
 14. The method of claim 10 further comprising: performing a chemical mechanical polishing process to remove excess gate contact oxide material.
 15. The method of claim 10 further comprising: performing a chemical mechanical polishing process to remove excess gate contact metal material.
 16. The method of claim 10, wherein each gate contact comprises a T-shaped profile.
 17. The method of claim 10, wherein the second gate nitride spacers are formed by an atomic layer deposition process.
 18. The method of claim 10, wherein each gate contact trench exposes a corresponding gate source/drain region in the substrate.
 19. The method of claim 18 further comprising: performing a source/drain implant process to the corresponding gate source/drain region.
 20. The method of claim 18, wherein each second gate nitride spacer has a uniform thickness and extends in a lengthwise direction perpendicular to the corresponding gate source/drain region.
-