

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12412701
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Takahashi; Tetsuhiro et al.

Dielectric composition and electronic component

Abstract

Provided is a dielectric composition containing: a main component expressed by $\{\text{Ba}_{1-x}\text{Ta}_{0.4}\text{O}_{12}\}_m$; and a first subcomponent, m satisfying a relationship of $1.95 \leq m \leq 2.40$. The first subcomponent includes silicon and magnesium. When the amount of the main component contained in the dielectric composition is set to 100 parts by mole, the amount of silicon contained in the dielectric composition is 7.5 to 15.0 parts by mole in terms of SiO_2 , and the amount of magnesium contained in the dielectric composition is 5.0 to 22.5 parts by mole in terms of MgO .

Inventors: Takahashi; Tetsuhiro (Tokyo, JP), Iguchi; Toshihiro (Tokyo, JP), Suzuki; Tomoko (Tokyo, JP)

Applicant: TDK Corporation (Tokyo, JP)

Family ID: 87520241

Assignee: TDK CORPORATION (Tokyo, JP)

Appl. No.: 17/982635

Filed: November 08, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230253154 A1	Aug. 10, 2023

Foreign Application Priority Data

JP	2022-016587	Feb. 04, 2022
----	-------------	---------------

Publication Classification

Int. Cl.: H01G4/12 (20060101); **C04B35/495** (20060101)

U.S. Cl.:

CPC **H01G4/1254** (20130101); **C04B35/495** (20130101); C04B2235/3206 (20130101); C04B2235/3232 (20130101); C04B2235/3244 (20130101); C04B2235/3255 (20130101); C04B2235/3256 (20130101); C04B2235/3262 (20130101); C04B2235/3418 (20130101); C04B2235/96 (20130101)

Field of Classification Search

CPC: H01G (4/1254); C04B (35/495); C04B (2235/3206); C04B (2235/3232); C04B (2235/3213); C04B (2235/3215)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2009/0086407	12/2008	Takahashi	361/321.5	C04B 35/638

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2000-103671	12/1999	JP	N/A

Primary Examiner: Orlando; Amber R

Assistant Examiner: Miller; Cameron K

Attorney, Agent or Firm: Oliff PLC

Background/Summary

(1) The present application claims a priority on the basis of Japanese patent application No. 2022-016587 filed on Feb. 4, 2022, which is incorporated herein by reference in its entirety.

TECHNICAL FIELD

(2) The present invention relates to a dielectric composition and an electronic component.

BACKGROUND

(3) For example, as disclosed in JP 2000-103671 A, a dielectric composition having a high specific dielectric constant without containing lead or an alkali metal has been developed.

(4) However, a novel dielectric composition that is being newly developed has a problem that a high-density dielectric substance is not obtained when not being fired at a high temperature.

SUMMARY

(5) The present invention has been made in consideration such circumstances, and an object thereof is to provide a novel dielectric composition in which a high sintering density is obtained even when being fired at a relatively low temperature, and a specific dielectric constant is high.

(6) According to an aspect of the present invention, there is provided a dielectric composition comprising: a main component expressed by $\{\text{Ba}_{x}\text{Sr}_{1-x}\}_{m}\text{Ta}_{.4}\text{O}_{12}$; and a first subcomponent, wherein m satisfies a relationship of $1.95 \leq m \leq 2.40$, the first subcomponent includes silicon and magnesium, the amount of silicon contained in the dielectric composition is

7.5 to 15.0 parts by mole in terms of SiO_2 , and the amount of magnesium contained in the dielectric composition is 5.0 to 22.5 parts by mole in terms of MgO , provided that the amount of the main component contained in the dielectric composition is set to 100 parts by mole.

(7) The dielectric composition according to the aspect of the present invention has a high sintering density and a high specific dielectric constant even when being fired at a relatively low temperature. The reason for this is not necessarily certain, but the following reason is considered. When m is within the above-described range, and a predetermined amount of silicon and magnesium is contained in the dielectric composition, it is considered that an operation of lowering a sintering initiation temperature is obtained. According to this, it is considered that even when being fired at a relatively low temperature, the high sintering density is easily obtained, and the specific dielectric constant is also improved.

(8) It is preferable that m satisfies a relationship of $2.10 \leq m \leq 2.40$. According to this, it is considered that an effect of improving wettability between the main component and the first subcomponent and lowering the sintering initiation temperature is obtained. According to this, even at a low temperature, a higher sintering density is obtained and the specific dielectric constant is further improved.

(9) Preferably, the dielectric composition further comprises at least one selected from the group consisting of manganese and at least one of rare-earth elements as a second subcomponent, the at least one selected from the group consisting of manganese and the at least one of rare-earth elements satisfies a predetermined amount in terms of a predetermined oxide in the dielectric composition, and wherein the predetermined amount of manganese contained in the dielectric composition is 0.5 to 7.0 parts by mole in terms of MnO , and/or the predetermined amount of the at least one of rare-earth elements expressed by RE and contained in the dielectric composition is 0.5 to 5.0 parts by mole in terms of RE_2O_3 , provided that the amount of the main component contained in the dielectric composition is set to 100 parts by mole.

(10) When the second subcomponent is contained in the dielectric composition within the above-described range, the sintering initiation temperature is further lowered. According to this, the sintering density is further improved, and the specific dielectric constant is further improved. In addition, when the second subcomponent is contained in the dielectric composition within the above-described range, an effect of improving resistance to reduction is obtained. As a result, a specific resistance is further improved.

(11) Preferably, the dielectric composition further contains at least one selected from the group consisting of titanium, hafnium, niobium, and molybdenum as a third subcomponent, the at least one selected from the group consisting of titanium, hafnium, niobium, and molybdenum is contained in the dielectric composition in an amount of 0.25 to 1.0 parts by mole in terms of a predetermined oxide, provided that the amount of the main component contained in the dielectric composition is set to 100 parts by mole, the amount of titanium is an amount in terms of TiO_2 , the amount of hafnium is an amount in terms of HfO_2 , the amount of niobium is an amount in terms of Nb_2O_5 , and the amount of molybdenum is an amount in terms of MoO_3 .

(12) When the third subcomponent is contained in the dielectric composition within the above-described range, the specific dielectric constant is further improved.

(13) It is preferable that the dielectric composition according to the present invention substantially does not contain alkali metal and lead.

(14) Examples of the dielectric composition that exhibits a high specific dielectric constant include $(\text{Na}, \text{K})\text{NbO}_3$ including an alkali metal, and $\text{Pb}(\text{Zr}, \text{Ti})\text{O}_3$ including lead.

(15) In addition, since the dielectric composition according to the present invention substantially does not contain an alkali metal, it is possible to prevent a composition deviation of the dielectric composition and contamination of a furnace due to evaporation of the alkali metal.

(16) Furthermore, although the use of lead is regulated by restriction of hazardous substances directive (RoHS), and the like, the dielectric composition according to the present invention

substantially does not contain lead.

(17) In addition, an electric component according to the present invention includes the above-described dielectric composition.

Description

BRIEF DESCRIPTION OF THE DRAWING(S)

(1) FIG. 1 is a schematic cross-sectional view of a multilayer ceramic capacitor according to an embodiment of the present invention; and

(2) FIG. 2 is a schematic cross-sectional view of a thin film capacitor according to an embodiment of the present invention.

DETAILED DESCRIPTION

First Embodiment

(3) <Multilayer Ceramic Capacitor>

(4) A multilayer ceramic capacitor **1** as an example of an electronic component according to an embodiment is illustrated in FIG. 1. The multilayer ceramic capacitor **1** includes an element body **10** in which a dielectric layer **2** and an inner electrode layer **3** are alternately stacked. A pair of outer electrodes **4** electrically connected to a plurality of the inner electrode layers **3** arranged alternately at the inside of the element body **10** are formed at both ends of the element body **10**. Although a shape of the element body **10** is not particularly limited, the shape is typically set to a rectangular parallelepiped shape. In addition, dimensions of the element body **10** are not particularly limited, and may be set to appropriate dimensions in correspondence with applications.

(5) <Dielectric Layer>

(6) The dielectric layer **2** is formed from a dielectric composition according to this embodiment to be described later.

(7) The thickness (interlayer thickness) of the dielectric layer **2** per one layer is not particularly limited, and can be set in correspondence with desired characteristics, applications, or the like. Typically, the interlayer thickness is preferably 30 μm or less, more preferably 15 μm or less, and still more preferably 10 μm or less.

(8) <Inner Electrode Layer>

(9) In this embodiment, the inner electrode layer **3** is staked so that respective ends are alternately exposed to two opposite end surfaces of the element body **10**.

(10) A conductive material contained in the inner electrode layer **3** is not particularly limited. Examples of a metal that is used as the conductive material include palladium, platinum, a silver-palladium alloy, nickel, a nickel-based alloy, copper, a copper-based alloy, and the like. Note that, various minor components such as phosphor and/or sulfur may be contained in nickel, the nickel-based alloy, copper, or the copper-based alloy in an amount of approximately 0.1% by mass or less. In addition, the inner electrode layer **3** can be formed by using commercially available paste for electrodes. The thickness of the inner electrode layer **3** may be appropriately determined in correspondence with applications or the like.

(11) <Outer Electrode>

(12) A conductive material contained in each of the outer electrodes **4** is not particularly limited. For example, known conductive materials such as nickel, copper, tin, silver, palladium, platinum, gold, alloys thereof, or a conductive resin may be used. The thickness of the outer electrode **4** may be appropriately determined in correspondence with applications or the like.

(13) <Dielectric Composition>

(14) The dielectric composition that constitutes the dielectric layer **2** according to this embodiment contains at least one of barium and strontium, and tantalum as a main component.

(15) The main component of the dielectric composition according to this embodiment preferably

includes strontium, and more preferably both strontium and barium.

(16) The main component of the dielectric composition according to this embodiment is expressed by $\{\text{Ba.sub.xSr.sub.(1-x)}\}\text{.sub.mTa.sub.4O.sub.2}$.

(17) x is preferably 0.75 or less, more preferably less than 0.75, and still more preferably 0.1 to 0.50.

(18) m preferably satisfies a relationship of $1.95 \leq m \leq 2.40$, and more preferably $2.10 \leq m \leq 2.40$.

(19) Although a crystal system of a crystal of the main component in the dielectric composition according to this embodiment is not particularly limited, the crystal is preferably a tetragonal system or an orthorhombic system, and more preferably the tetragonal system.

(20) Note that, in this embodiment, when the amount of elements contained in the dielectric composition other than oxygen is set to 100 parts by mole, the elements constituting the main component other than oxygen occupy 70 to 99.5 parts by mole.

(21) In addition, the dielectric composition according to this embodiment substantially does not contain an alkali metal, and lead. Description of “substantially does not contain an alkali metal, and lead” represents that when the amount of elements contained in the dielectric composition other than oxygen is set to 100 parts by mole, the sum of “an alkali metal, and lead” is 10 parts by mole or less, and preferably 5 parts by mole or less.

(22) The dielectric composition according to this embodiment contains silicon and magnesium as a first subcomponent.

(23) When the amount of the main component contained in the dielectric composition is set to 100 parts by mole, the amount of silicon contained in the dielectric composition is 7.5 to 15.0 parts by mole in terms of SiO_2 , and preferably 10.0 to 13.5 parts by mole.

(24) That is, the amount of silicon contained is obtained in terms of an oxide when the valence of silicon is tetravalent.

(25) When the amount of the main component contained in the dielectric composition is set to 100 parts by mole, the amount of magnesium contained in the dielectric composition is 5.0 to 22.5 parts by mole in terms of MgO , and preferably 7.0 to 12.5 parts by mole. That is, the amount of magnesium contained is obtained in terms of an oxide when the valence of magnesium is divalent.

(26) The dielectric composition according to this embodiment preferably contain at least one selected from the group consisting of manganese and a rare-earth element as a second subcomponent.

(27) When the amount of the main component contained in the dielectric composition is set to 100 parts by mole, the amount of manganese contained in the dielectric composition is 0.5 to 7.0 parts by mole in terms of MnO . That is, the amount of manganese contained is obtained in terms of an oxide when the valence of manganese is divalent.

(28) The rare-earth element is expressed by “RE”. When the amount of the main component contained in the dielectric composition is set to 100 parts by mole, the amount of the rare-earth element (RE) contained is 0.5 to 5.0 parts by mole in terms of RE_2O_3 . That is, the amount of the rare-earth element contained is obtained in terms of an oxide when the valence of the rare-earth element is trivalent.

(29) The dielectric composition according to this embodiment preferably contains at least one selected from the group consisting of titanium, hafnium, niobium, and molybdenum as a third subcomponent.

(30) Specifically, when the amount of the main component contained in the dielectric composition is set to 100 parts by mole, at least one selected from the group consisting of titanium, hafnium, niobium, and molybdenum is preferably contained in the dielectric composition in an amount of 0.25 to 1.0 parts by mole in terms of a predetermined oxide.

(31) The amount of titanium contained is an amount in terms of TiO_2 . That is, the amount of titanium contained is obtained in terms of an oxide when the valence of titanium is tetravalent.

(32) The amount of hafnium contained is an amount in terms of HfO_2 . That is, the amount of

hafnium contained is obtained in terms of an oxide when the valence of hafnium is tetravalent.
(33) The amount of niobium contained is an amount in terms of Nb_2O_5 . That is, the amount of niobium contained is obtained in terms of an oxide when the valence of niobium is pentavalent.

(34) The amount of molybdenum contained is an amount in terms of MoO_3 . That is, the amount of molybdenum contained is obtained in terms of an oxide when the valence of molybdenum is hexavalent.

(35) The dielectric composition according to this embodiment may contain aluminum, calcium, chromium, vanadium, zirconium, tungsten, and the like in addition to the above main component, the first subcomponent, the second subcomponent, and the third subcomponent.

(36) <Method of Manufacturing Multilayer Ceramic Capacitor>

(37) Next, description will be given of an example of a method of manufacturing the multilayer ceramic capacitor **1** illustrated in FIG. **1**.

(38) In this embodiment, a powder of the main component that constitutes the dielectric composition, and powders of the first subcomponent, the second subcomponent, and the third subcomponent are prepared, respectively. Although a method preparing the powder of the main component is not particularly limited, the powder can be prepared by a solid phase reaction method such as calcination. Raw materials of respective elements which constitute the powder of the main component, and the powders of the first subcomponent, the second subcomponent, and the third subcomponent are not particularly limited, and oxides of the respective elements can be used. In addition, various kinds of compounds from which oxides of the respective elements can be obtained by firing can be used.

(39) Raw materials of the powder of the main component, and the powders of the first subcomponent, the second subcomponent, and the third subcomponent are weighed in a predetermined ratio, and wet mixing is performed for predetermined time by using a ball mill, or the like. The resultant mixed powder is dried and subjected to a heat treatment in a range of 700° C. to 1300° C. in the air to obtain a calcined powder of the main component, the first subcomponent, the second subcomponent, and the third subcomponent. In addition, the calcined powder may be pulverized for predetermined time by using a ball mill, or the like.

(40) Next, paste for manufacturing a green chip is prepared. The obtained calcined powder and a solvent are kneaded to form a paint, thereby preparing paste for the dielectric layer. Known binder and the solvent may be used.

(41) The paste for the dielectric layer may contain an additive such as a plasticizer and a dispersant as necessary.

(42) A paste for the inner electrode layer is obtained by kneading a raw material of the above-described conductive material, a binder, and a solvent. Known binder and solvent may be used. The paste for the inner electrode layer may contain an additive such as an inhibitor and a plasticizer as necessary.

(43) A paste for the outer electrode can be prepared in the same manner as in the paste for the inner electrode layer.

(44) A green sheet and an inner electrode pattern are formed by using the obtained pastes, and the green sheet and the inner electrode pattern are stacked to obtain a green chip.

(45) The obtained green chip is subjected to a binder removal treatment as necessary. As binder removal treatment conditions, for example, a holding temperature is preferably set to 200° C. to 350° C.

(46) After the binder removal treatment, the green chip is fired to obtain the element body **10**. In this embodiment, a firing atmosphere is not particularly limited, and firing may be performed in the air or a reducing atmosphere. In this embodiment, the holding temperature at the time of firing is, for example, 1150° C. to 1250° C.

(47) After the firing, the obtained element body **10** is subjected to a reoxidation treatment

(annealing) as necessary. As annealing conditions, for example, an oxygen partial pressure at the time of annealing is preferably set to an oxygen partial pressure higher than an oxygen partial pressure at the timing of firing, and a holding temperature is preferably set to 1150° C. or lower.

(48) A dielectric composition that constitutes the dielectric layer **2** of the element body **10** obtained as described above is the above-described dielectric composition. The element body **10** is subjected to end surface polishing, the paste for the outer electrode is applied and is preliminarily fired to form the outer electrode **4**. Then, a coating layer is formed on a surface of the outer electrode **4** by plating or the like as necessary.

(49) As described above, the multilayer ceramic capacitor **1** according to this embodiment is manufactured.

(50) The dielectric composition according to this embodiment contains {Ba.sub.xSr.sub.(1-x)}.sub.mTa.sub.4O.sub.12 as the main component, m is within a predetermined range, and the dielectric composition contains a predetermined amount of silicon and magnesium as the first subcomponent. According to this, it is possible to obtain a dielectric composition having a high sintering density and a high specific dielectric constant even when the dielectric composition is sintered by firing the dielectric composition at a relatively low temperature.

(51) The reason for this is not necessarily certain, but the following reason is considered. When m is within the above-described range, and a predetermined amount of silicon and magnesium is contained in the dielectric composition, it is considered that an operation of lowering a sintering initiation temperature is obtained. According to this, it is considered that even when being fired at a relatively low temperature, the high sintering density is easily obtained, and the specific dielectric constant is also improved.

(52) In addition, according to this embodiment, it is possible to obtain a dielectric composition that substantially does not contain an alkali metal and lead, and exhibits a high density, a high specific dielectric constant, a low dielectric loss, and a high specific resistance.

Second Embodiment

(53) <Thin Film Capacitor>

(54) A schematic view of a thin film capacitor **11** according to this embodiment is shown in FIG. 2. In the thin film capacitor **11** illustrated in FIG. 2, a lower electrode **112** and a dielectric thin film **113** are formed on a substrate **111** in this order, and an upper electrode **114** is provided on a surface of the dielectric thin film **113**.

(55) Although a material of the substrate **111** is not particularly limited, when using a silicon single crystal substrate is used as the substrate **111**, availability and cost are excellent. When flexibility is emphasized, nickel foil or copper foil can also be used as the substrate.

(56) A material of the lower electrode **112** and the upper electrode **114** is not particularly limited, and the material may function as an electrode. Examples of the material include platinum, silver, nickel, and the like. The thickness of the lower electrode **112** is not particularly limited, and the thickness is, for example, 0.01 to 10 μm. The thickness of the upper electrode **114** is not particularly limited, and the thickness is, for example, 0.01 to 10 μm.

(57) A composition of a dielectric composition that constitutes the dielectric thin film **113** and a crystal system of a main component according to this embodiment are similar as in the first embodiment.

(58) Although the thickness of the dielectric thin film **113** is not particularly limited, but the thickness is preferably 10 nm to 1 μm.

(59) <Method of Manufacturing Thin Film Capacitor>

(60) Next, a method of manufacturing the thin film capacitor **11** will be described.

(61) There is no particular limitation to a film formation method of a thin film that finally becomes the dielectric thin film **113**. Examples of the method include a vacuum deposition method, a sputtering method, a pulsed laser deposition method (PLD method), a metalorganic chemical vapor deposition method (MO-CVD method), a metalorganic decomposition method (MOD method), a

sol-gel method, a chemical solution deposition method (CSD method), and the like.

(62) In addition, a minute impurity or subcomponent may be contained in a raw material that is used in film formation, but there is no particular problem as long as the impurity or the subcomponent is contained in an amount that does not greatly damage the performance of the thin film. In addition, the dielectric thin film **113** according to this embodiment may contain minute impurities or subcomponents in an amount that does not greatly damage the performance.

(63) In this embodiment, a film formation method by the PLD method will be described.

(64) First, a silicon single crystal substrate is prepared as the substrate **111**. Next, films of SiO₂, TiO_x, and platinum are sequentially formed on the silicon single crystal substrate, and the lower electrode **112** formed from platinum is formed. A method of forming the lower electrode **112** is not particularly limited. Examples of the method include a sputtering method, a CVD method, and the like.

(65) Next, the dielectric thin film **113** is formed on the lower electrode **112** by the PLD method. In addition, a region where a thin film is not partially formed may be formed by using a metal mask so as to expose a part of the lower electrode **112**.

(66) In the PLD method, first, a target containing a constituent element of the dielectric thin film **113** that is desired is provided in a film formation chamber. Next, a surface of the target is irradiated with a pulsed laser. The surface of the target instantly vaporizes due to strong energy of the pulsed laser. Then, an evaporated material is deposited on the substrate disposed to face the target to form the dielectric thin film **113**.

(67) The type of the target is not particularly limited, and in addition to a metal oxide sintered body containing the constituent element of the dielectric thin film **113** to be manufactured, an alloy or the like can be used. In addition, it is preferable that respective elements are evenly distributed in the target, but a variation may exist in the distribution within a range having no influence on the quality of the dielectric thin film **113** to be obtained.

(68) It is not necessary for the target to be one piece, and a plurality of targets containing parts of the constituent elements of the dielectric thin film **113** may be prepared to be used in film formation. A shape of the target is not limited, and the shape may be set to a shape suitable for a film formation device that is used.

(69) In addition, in the PLD method, it is preferable to heat the substrate **111** with an infrared laser at the timing of film formation so as to crystallize the dielectric thin film **113** that is formed. A heating temperature of the substrate **111** varies in accordance with constituent elements, and the composition, and the like of the dielectric thin film **113** and the substrate **111**, but the film formation is performed by heating the substrate **111** to be, for example, 600° C. to 800° C. When the temperature of the substrate **111** is set to an appropriate temperature, the dielectric thin film **113** is likely to be crystallized and occurrence of cracks during cooling can be prevented.

(70) Finally, the upper electrode **114** is formed on the dielectric thin film **113**, thereby manufacturing the thin film capacitor **11**. Note that, a material of the upper electrode **114** is not particularly limited, and silver, gold, copper, or the like can be used. In addition, there is no particular limitation to a method of forming the upper electrode **114**. For example, the upper electrode **114** can be formed by deposition, or a sputtering method.

(71) Hereinbefore, the embodiment of the present invention has been described, but the present invention is not limited to the embodiment and the like, and it should be understood that the present invention can be executed in various different aspects within a range not departing from the gist of the present invention.

(72) In the above-described embodiments, description has been given of a case where the electronic component according to the present invention is a multilayer ceramic capacitor, but the electronic component according to the present invention is not limited to the multilayer ceramic capacitor, and may be any electronic component including the above-described dielectric composition.

(73) For example, the above-described electronic component may be a single plate type ceramic

capacitor in which a pair of electrodes is formed on a single-layer dielectric substrates formed from the dielectric composition.

(74) In addition, the electronic component according to the present invention may be a filter, a diplexer, a resonator, an oscillator, an antenna, or the like in addition to the capacitor.

EXAMPLES

(75) Hereinafter, the present invention will be described in more detail with reference to examples and comparative examples. However, the present invention is not limited to the following examples.

(76) Powders of barium carbonate (BaCO_3), strontium carbonate (SrCO_3), and tantalum oxide (Ta_2O_5) were prepared as starting raw materials of the main component of the dielectric composition. The prepared starting raw materials of the main component were weighed so that x in the composition of the main component expressed by $\{\text{Ba}_x\text{Sr}_{(1-x)}\text{Ta}_m\text{O}_2\}$ becomes 0.5 in Table 1 and Table 2, and becomes as described in Table 3, and m becomes as described in Table 1 to Table 3.

(77) In addition, respective raw material powders were prepared as starting raw materials of the first subcomponent, the second subcomponent, and the third subcomponent of the dielectric composition, and the prepared starting raw materials of the first subcomponent, the second subcomponent, and the third subcomponent were weighed so that the amounts of the first subcomponent, the second subcomponent, and the third subcomponent after firing become as described in Table 1 to Table 3. Note that, “the amounts of the first subcomponent, the second subcomponent, and the third subcomponent” are “amounts of the first subcomponent, the second subcomponent, and the third subcomponent contained in the dielectric composition in terms a predetermined oxide when the amount of the main component contained in the dielectric composition is set to 100 parts by mole”.

(78) Next, the respective weighed powders were wet-mixed with a ball mill by using an ion exchanged water as a dispersion medium, and the resultant mixture was dried to obtain a mixed raw material powder. Then, the obtained mixed raw material powder was subject to a heat treatment in the air under conditions of a holding temperature of 900° C. and holding time of two hours to obtain a calcined powder.

(79) The obtained calcined powder was wet-pulverized with a ball mill by using an ion exchanged water as a dispersion medium and was dried to obtain a dielectric raw material.

(80) 10 parts by mass of aqueous solution containing 6 parts by mass of polyvinyl alcohol resin as a binder was added to 100 parts by mass of dielectric raw material obtained, and the resultant mixture was granulated to obtain a granulated powder.

(81) The obtained granulated powder was put into a mold having a diameter ϕ of 12 mm, was subjected to temporary press-molding at a pressure of 0.6 ton/cm², and was subjected to main press-molding at a pressure of 1.2 ton/cm² to obtain a disc-shaped green molded body.

(82) Next, the obtained green molded body was subjected to a binder removal treatment, firing, and annealing under the following conditions to obtain an element body.

(83) Binder removal treatment conditions were set as follows. That is, a holding temperature was set to 400° C., temperature holding time was set to two hours, and an atmosphere was set to the air.

(84) As firing conditions, a holding temperature was set to 1250° C., temperature holding time was set to two hours, and an atmosphere was set to a humidified N_2+H_2 mixed gas (an oxygen partial pressure: 10⁻¹² MPa). Note that, a wetter was used to humidify the atmospheric gas during firing.

(85) As annealing conditions, a holding temperature was set to 1050° C., temperature holding time was set to two hours, and an atmospheric gas was set to a humidified N_2 gas (an oxygen partial pressure: 10⁻⁷ MPa). Note that, a wetter was used to humidify the atmospheric gas during annealing.

(86) A sintering density, a specific dielectric constant, and a specific resistance of the obtained

sintered body (dielectric composition) were investigated by the following method. Note that, in order to measure the specific dielectric constant and the specific resistance, an In—Ga electrode is applied to the dielectric composition (sintered body), thereby obtaining a disc-shaped ceramic capacitor sample (capacitor sample).

(87) <Sintering Density>

(88) The sintering density of the dielectric composition was measured as follows. First, a volume V of the dielectric composition was calculated. Next, a mass M of the disc-shaped dielectric composition was measured, and MN was calculated to obtain the sintering density of the dielectric composition. Results are shown in Table 1 to Table 3.

(89) <Specific Dielectric Constant>

(90) A signal having a frequency of 1 kHz and an input signal level (measurement voltage) of 1 V/rms was input to the capacitor sample at room temperature (20° C.) by using a digital LCR meter (4284A, manufactured by YHP) to measure electrostatic capacitance C. Then, the specific dielectric constant was calculated on the basis of the thickness of the dielectric composition, an effective electrode area, and the electrostatic capacitance C obtained as a result of measurement. Results are shown in Table 1 to Table 3.

(91) <Specific Resistance>

(92) An insulation resistance of the capacitor sample was measured at a reference temperature (25° C.) by using a digital resistance meter (R8340, manufactured by ADVANTEST CORPORATION). The specific resistance was calculated from the obtained insulation resistance, the effective electrode area, and the thickness of the dielectric composition. Results are shown in Table 1 to Table 3.

(93) TABLE-US-00001 TABLE 1 Amount of first subcomponent subcomponent
Amount of third subcomponent contained contained contained Si Mg Mn RE Ti Hf Nb Mo Specific
In terms In terms In terms In terms In terms In terms In terms In terms Sintering dielectric Specific
Sample of SIO₂ of MgO of Mno of RE.sub.2O.sub.2 of TIO.sub.2 of HfO.sub.2 of
Nb.sub.2O.sub.5 of MoO.sub.3 density constant resistance No. m (mol) (mol) (mol) (mol) (mol)
(mol) (mol) (mol) (g/cm.sup.3) (—) (Ω .Math. m) 1 1.90 5.00 0.00 0.00 0.00 0.00 0.00 0.00 0.00
3.89 48 8.4E+09 2 1.90 5.00 2.50 0.00 0.00 0.00 0.00 0.00 0.00 4.87 50 1.2E+10 3 1.90 8.50 6.50
0.00 0.00 0.00 0.00 0.00 0.00 5.54 62 2.3E+10 4 1.90 15.00 10.00 0.00 0.00 0.00 0.00 0.00
6.21 64 8.1E+10 5 1.95 8.50 6.50 0.00 0.00 0.00 0.00 0.00 0.00 6.60 78 1.8E+11 6 2.00 8.50 6.50
0.00 0.00 0.00 0.00 0.00 0.00 6.70 80 3.5E+11 7 2.05 8.50 6.50 0.00 0.00 0.00 0.00 0.00 6.79
82 3.3E+11 8 2.10 8.50 6.50 0.00 0.00 0.00 0.00 0.00 0.00 7.10 108 6.0E+11 9 2.20 8.50 6.50 0.00
0.00 0.00 0.00 0.00 0.00 7.07 106 7.1E+11 10 2.30 8.50 6.50 0.00 0.00 0.00 0.00 0.00 7.10
109 6.5E+11 11 2.40 8.50 6.50 0.00 0.00 0.00 0.00 0.00 0.00 7.08 105 5.3E+11 12 2.45 8.50 6.50
0.00 0.00 0.00 0.00 0.00 0.00 6.70 65 7.7E+11 13 2.50 13.50 12.50 0.00 0.00 0.00 0.00 0.00
6.90 60 9.2E+11 14 2.05 0.00 0.00 0.00 0.00 0.00 0.00 0.00 0.00 3.65 38 2.0E+09 15 2.05 5.00
5.00 0.00 0.00 0.00 0.00 0.00 0.00 4.90 54 1.4E+10 16 2.05 7.50 5.00 0.00 0.00 0.00 0.00 0.00
6.63 79 1.9E+11 17 2.05 10.00 5.00 0.00 0.00 0.00 0.00 0.00 0.00 6.82 85 3.1E+11 18 2.05 11.00
5.00 0.00 0.00 0.00 0.00 0.00 0.00 6.84 87 3.3E+11 19 2.05 12.50 5.00 0.00 0.00 0.00 0.00
0.00 6.88 88 5.0E+11 20 2.05 13.50 5.00 0.00 0.00 0.00 0.00 0.00 6.90 86 3.9E+11 21 2.05
15.00 5.00 0.00 0.00 0.00 0.00 0.00 0.00 6.85 76 5.5E+11 22 2.05 20.00 5.00 0.00 0.00 0.00
0.00 0.00 6.90 66 6.3E+11 23 2.05 8.50 0.00 0.00 0.00 0.00 0.00 0.00 4.22 53 2.6E+10 24
2.05 8.50 2.50 0.00 0.00 0.00 0.00 0.00 0.00 6.22 58 9.1E+10 25 2.05 8.50 5.00 0.00 0.00 0.00
0.00 0.00 6.59 75 3.2E+11 26 2.05 8.50 7.00 0.00 0.00 0.00 0.00 0.00 6.84 83 4.4E+11 27
2.05 8.50 10.00 0.00 0.00 0.00 0.00 0.00 0.00 6.88 86 4.2E+11 28 2.05 8.50 12.50 0.00 0.00 0.00
0.00 0.00 0.00 6.88 88 5.1E+11 29 2.05 8.50 15.00 0.00 0.00 0.00 0.00 0.00 6.90 79 4.8E+11
30 2.05 8.50 17.50 0.00 0.00 0.00 0.00 0.00 0.00 6.88 76 5.1E+11 31 2.05 8.50 20.00 0.00 0.00
0.00 0.00 0.00 0.00 6.90 75 5.5E+11 32 2.05 8.50 22.50 0.00 0.00 0.00 0.00 0.00 6.88 74
6.8E+11 33 2.05 8.50 25.00 0.00 0.00 0.00 0.00 0.00 6.86 68 8.9E+11

x)}_{1-x}}.sub.mTa.sub.4O.sub.12 satisfies a relationship of $2.10 \leq m \leq 2.40$, the amount of silicon contained is 7.5 to 15.0 parts by mole in terms of SiO₂, the amount of magnesium contained is 5.0 to 22.5 parts by mole in terms of MgO, at least one selected from the group consisting of manganese and a rare-earth element satisfies a predetermined amount in terms of a predetermined oxide, the predetermined amount of manganese contained is 0.5 to 7.0 parts by mole in terms of MnO, and the predetermined amount of the rare-earth element (RE) contained is 0.5 to 5.0 parts by mole in terms of RE₂O₃ (Samples Nos. 42 to 50 and 52 to 63), the sintering density is 7.20 g/cm³ or greater, the specific dielectric constant is 120 or greater, and the specific resistance is 1.0×10^{12} or greater.

(99) From Table 1 to Table 3, it could be confirmed that in a case where m in {Ba_xSr_{1-x}}.sub.mTa.sub.4O.sub.12 satisfies a relationship of $2.10 \leq m \leq 2.40$, the amount of silicon contained is 7.5 to 15.0 parts by mole in terms of SiO₂, the amount of magnesium contained is 5.0 to 22.5 parts by mole in terms of MgO, at least one selected from the group consisting of manganese and a rare-earth element satisfies a predetermined amount in terms of a predetermined oxide, the predetermined amount of manganese contained is 0.5 to 7.0 parts by mole in terms of MnO, and the predetermined amount of the rare-earth element (RE) contained is 0.5 to 5.0 parts by mole in terms of RE₂O₃, and the amount of at least one among titanium, hafnium, niobium, and molybdenum is 0.25 to 1.0 parts by mole in terms of a predetermined oxide (Samples Nos. 56 to 63), the sintering density is 7.20 g/cm³ or greater, the specific dielectric constant is 130 or greater, and the specific resistance is 1.0×10^{12} or greater.

NUMERICAL REFERENCES

(100) **1** MULTILAYER CERAMIC CAPACITOR **10** ELEMENT BODY **2** DIELECTRIC LAYER
3 INNER ELECTRODE LAYER **4** OUTER ELECTRODE **11** THIN FILM CAPACITOR **111**
SUBSTRATE **112** LOWER ELECTRODE **113** POLYCRYSTALLINE DIELECTRIC THIN FILM
114 UPPER ELECTRODE

Claims

1. A dielectric composition, comprising: a main component expressed by {Ba_xSr_{1-x}}.sub.mTa.sub.4O.sub.2; and a first subcomponent, wherein m satisfies a relationship of $1.95 \leq m \leq 2.40$, the first subcomponent includes silicon and magnesium, the amount of silicon contained in the dielectric composition is 7.5 to 15.0 parts by mole in terms of SiO₂, and the amount of magnesium contained in the dielectric composition is 5.0 to 22.5 parts by mole in terms of MgO, provided that the amount of the main component contained in the dielectric composition is set to 100 parts by mole.
2. The dielectric composition according to claim 1, wherein m satisfies a relationship of $2.10 \leq m \leq 2.40$.
3. The dielectric composition according to claim 1, further comprising: at least one selected from the group consisting of manganese and at least one of rare-earth elements as a second subcomponent, wherein the at least one selected from the group consisting of manganese and the at least one of rare-earth elements satisfies a predetermined amount in terms of a predetermined oxide in the dielectric composition, and wherein the predetermined amount of manganese contained in the dielectric composition is 0.5 to 7.0 parts by mole in terms of MnO, and/or the predetermined amount of the at least one of rare-earth elements expressed by RE and contained in the dielectric composition is 0.5 to 5.0 parts by mole in terms of RE₂O₃, provided that the amount of the main component contained in the dielectric composition is set to 100 parts by mole.
4. The dielectric composition according to claim 1, further comprising: at least one selected from the group consisting of titanium, hafnium, niobium, and molybdenum as a third subcomponent, wherein the at least one selected from the group consisting of titanium, hafnium, niobium, and molybdenum is contained in the dielectric composition in an amount of 0.25 to 1.0 parts by mole in

terms of a predetermined oxide, provided that the amount of the main component contained in the dielectric composition is set to 100 parts by mole, the amount of titanium is an amount in terms of TiO_2 , the amount of hafnium is an amount in terms of HfO_2 , the amount of niobium is an amount in terms of Nb_2O_5 , and the amount of molybdenum is an amount in terms of MoO_3 .

5. An electronic component comprising: the dielectric composition according to claim 1.
