

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250280586

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

CHO; Min Su et al.

POWER SEMICONDUCTOR DEVICE AND METHOD OF MANUFACTURING SAME

Abstract

Proposed are a power semiconductor device and a method of manufacturing the same seeking to increase a current path area and to capture electrons trapped between a gate electrode and a drain electrode to prevent current collapse effects by forming a plurality of hole injection regions spaced apart from each other at the bottom of the drain electrode.

Inventors: CHO; Min Su (Eumseong-gun, KR), KIM; Dae Il (Eumseong-gun, KR), JUNG; Ji Houn (Eumseong-gun, KR), LEE; Hee Sub (Eumseong-gun, KR), SON; Ung Bi (Eumseong-gun, KR), LEE; Jun Hyeok (Eumseong-gun, KR)

Applicant: DB HiTek Co., Ltd. (Bucheon-si, KR)

Family ID: 96880779

Appl. No.: 18/635711

Filed: April 15, 2024

Foreign Application Priority Data

KR

10-2024-0030653

Mar. 04, 2024

Publication Classification

Int. Cl.: H01L29/417 (20060101); H01L29/20 (20060101); H01L29/40 (20060101); H01L29/66 (20060101); H01L29/778 (20060101)

U.S. Cl.:

CPC H10D64/256 (20250101); H10D30/015 (20250101); H10D30/475 (20250101); H10D62/8503 (20250101); H10D64/01 (20250101); H10D64/112 (20250101);

Background/Summary

CROSS REFERENCE TO RELATED APPLICATION

[0001] The present application claims priority to Korean Patent Application No. 10-2024-0030653, filed Mar. 4, 2024, the entire contents of which is incorporated herein for all purposes by this reference.

BACKGROUND OF THE INVENTION

Field of the Invention

[0002] The present disclosure relates to a power semiconductor device and a method of manufacturing the same and, more particularly, to a power semiconductor device and a method of manufacturing the same seeking to increase a current path area and to capture electrons trapped between a gate electrode and a drain electrode to prevent current collapse effects by forming a plurality of hole injection regions spaced apart from each other at the bottom of the drain electrode.

Description of the Related Art

[0003] Nitride semiconductors are being applied to high-voltage and high-power semiconductor devices due to their high electron saturation velocity and wide-bandgap (WBG) properties. In particular, gallium nitride (GaN) has wider band gap and higher breakdown electric field properties compared to silicon and gallium arsenide (GaAs), and thus shows excellent breakdown voltage characteristics when applied to transistors.

[0004] In addition, since gallium nitride (GaN)-based devices have higher electron mobility and electron saturation velocity compared to silicon-based devices that are currently commonly used, they may exhibit high frequency characteristics. When applied to a GaN device, the high electron mobility leads to improved on-resistance characteristics, and thus allows for the implementation of a low-loss switching device.

[0005] As such, GaN-based field effect transistors (FETs) have great advantages as devices that are suitable for high frequency and high power applications, and for this reason, continuous research is being conducted thereon. Although much progress has been made in the research and development of GaN-based FETs over the past few years, there are still several issues that need to be addressed regarding device reliability. One of the important issues is related to current collapse effects caused by traps existing in semiconductors.

[0006] FIG. 1 is a partial cross-sectional view of a conventional power semiconductor device.

[0007] Hereinafter, the schematic structure and problems of a conventional power semiconductor device 9 will be described in detail with reference to the accompanying drawings.

[0008] Referring to FIG. 1, in the conventional power semiconductor device 9, a higher voltage than the voltage applied to a source electrode 910 and a gate electrode 930 may be applied to a drain electrode 950. In this case, carriers may be trapped between the gate electrode 930 and the drain electrode 950. Due to the carrier trapping, a current collapse phenomenon occurs, and this current collapse may cause a “memory effect” in which conduction current of a device may vary depending on how long a previously applied voltage has been present. For example, during transistor operation, electrons are trapped in an epitaxial layer or a dielectric layer, and at this time, the trapped electrons may repel electrons traveling through a channel, impeding current conduction through a two-dimensional electron gas (2DEG) layer 970. This may immediately cause a problem of increasing the resistance of the channel.

[0009] To solve the above-mentioned problems, the present disclosure proposes a novel power semiconductor device with improved structure and a method of manufacturing the same.

DOCUMENTS OF RELATED ART

[0010] (Patent Document 0001) Korean Patent Application Publication No. 10-2020-0068745 “HIGH ELECTRON MOBILITY TRANSISTOR”

SUMMARY OF THE INVENTION

[0011] The present disclosure has been made to solve the problems of the related art, and an objective of the present disclosure is to provide a power semiconductor device and a method of manufacturing the same seeking to capture electrons trapped between a gate electrode and a drain electrode to prevent current collapse effects by forming a plurality of hole injection regions spaced apart from each other at the bottom of the drain electrode.

[0012] An objective of the present disclosure is to provide a power semiconductor device and a manufacturing method thereof seeking to increase the total area of a current path by increasing a junction area between GaN of a channel layer and a metal layer such as Ti of a drain electrode by forming a plurality of protruding regions that protrude downward on the lower side of the drain electrode to be spaced apart.

[0013] An objective of the present disclosure is to provide a power semiconductor device and a manufacturing method thereof seeking to ensure process uniformity by etching a barrier layer and a channel layer located in the space between hole injection regions.

[0014] An objective of the present disclosure is to provide a power semiconductor device and a manufacturing method thereof seeking to reduce an electric field between a gate electrode and a drain electrode by forming a first field plate and/or a second field plate on the side spaced apart from the gate electrode.

[0015] An objective of the present disclosure is to provide a power semiconductor device and a manufacturing method thereof seeking to reduce an electric field between a gate electrode and a drain electrode by having the drain electrode form a wing portion.

[0016] The present disclosure may be implemented by an embodiment having the following configuration to achieve the above-described objectives.

[0017] According to an embodiment of the present disclosure, there is provided a power semiconductor device, including: a substrate; a channel layer having a first nitride-based semiconductor layer and disposed on the substrate; a barrier layer disposed on the channel layer and having a second nitride-based semiconductor layer that is different from the first nitride-based semiconductor layer of the channel layer; a capping layer having an impurity doped region of a first conductivity type and disposed on the barrier layer; a gate electrode disposed on the capping layer; a plurality of hole injection regions, each having an impurity doped region of a first conductivity type, each being laterally spaced apart from another on the barrier layer; and a drain electrode in contact with the plurality of hole injection regions.

[0018] According to another embodiment of the present disclosure, in the power semiconductor device, the drain electrode may include a plurality of protruding regions, each being disposed at a bottom of the drain electrode in a space between the plurality of hole injection regions.

[0019] According to still another embodiment of the present disclosure, in the power semiconductor device, the plurality of protruding regions may have bottoms thereof extending into the channel layer.

[0020] According to still another embodiment of the present disclosure, in the power semiconductor device, an upper surface of the channel layer below each of the plurality of hole injection regions may be disposed at a higher position than an upper surface of the channel layer below each of the plurality of protruding regions.

[0021] According to still another embodiment of the present disclosure, in the power semiconductor device, the capping layer may have a greater top to bottom thickness compared to a top to bottom thickness of each of the plurality of hole injection regions.

[0022] According to still another embodiment of the present disclosure, in the power semiconductor device, the plurality of hole injection regions may be spaced apart from each other in an island pattern.

[0023] According to still another embodiment of the present disclosure, in the power semiconductor device, the plurality of hole injection regions may be laterally spaced from each

other in a stripe pattern.

[0024] According to still another embodiment of the present disclosure, in the power semiconductor device, the drain electrode may further include a wing portion that protrudes a predetermined length from a predetermined height of the drain electrode toward a side adjacent to the gate electrode.

[0025] According to still another embodiment of the present disclosure, the power semiconductor device may further include: an insulating film covering the gate electrode and the drain electrode; and a first field plate disposed apart from the gate electrode within the insulating film, wherein the first field plate may be electrically connected to the gate electrode.

[0026] According to still another embodiment of the present disclosure, the power semiconductor device may further include: a source electrode disposed apart from the gate electrode; and a second field plate disposed apart from the gate electrode within an insulating film, wherein the second field plate may be electrically connected to the source electrode.

[0027] According to still another embodiment of the present disclosure, there is provided a power semiconductor device, including: a substrate; a channel layer having a first nitride-based semiconductor layer and disposed on the substrate; a barrier layer disposed on the channel layer and having a second nitride-based semiconductor layer that is different from the first nitride-based semiconductor layer of the channel layer; a capping layer having an impurity doped region of a first conductivity type and disposed on the barrier layer; a gate electrode disposed on the capping layer; a plurality of hole injection regions, each having an impurity doped region of a first conductivity type and laterally disposed apart from another on the barrier layer; a source electrode disposed apart from the gate electrode; and a drain electrode disposed apart from the gate electrode and including a plurality of protruding regions, each being disposed in a space between the plurality of hole injection regions.

[0028] According to still another embodiment of the present disclosure, in the power semiconductor device, the capping layer may have a thickness that is substantially the same as a thickness of each of the plurality of hole injection regions.

[0029] According to still another embodiment of the present disclosure, the power semiconductor device may further include: an insulating film covering the gate electrode, the source electrode, and the drain electrode; a first field plate disposed apart from the gate electrode within the insulating film; and a second field plate disposed apart from the first field plate within the insulating film, wherein the first field plate may be electrically connected to the gate electrode and the second field plate may be electrically connected to the source electrode.

[0030] According to still another embodiment of the present disclosure, in the power semiconductor device, each of the plurality of protruding regions may have a longer vertical length than a vertical length of each of the plurality of hole injection regions adjacent thereto.

[0031] According to an embodiment of the present disclosure, there is provided a method of manufacturing a power semiconductor device, the method including: forming a channel layer having a first nitride-based semiconductor layer on a substrate; forming a barrier layer having a second nitride-based semiconductor layer that is different from the first nitride-based semiconductor layer on the channel layer; forming a capping layer of a first conductivity type on the barrier layer; forming a plurality of hole injection regions on the barrier layer apart from the capping layer; forming a first insulating film layer on the barrier layer to cover the capping layer and the plurality of hole injection regions; and forming a source electrode and a drain electrode after etching the first insulating film layer.

[0032] According to another embodiment of the present disclosure, in the method of manufacturing a power semiconductor device, the plurality of hole injection regions may be provided to be spaced apart from each other by forming a first doped layer on the barrier layer and then etching the first doped layer using a mask pattern.

[0033] According to still another embodiment of the present disclosure, in the method of

manufacturing a power semiconductor device, the drain electrode may be provided by forming a plurality of trenches by etching the barrier layer and the channel layer beneath a plurality of spaces separating the plurality of hole injection regions from each other, forming a doped layer of a first conductivity type to cover the plurality of hole injection regions and fill the plurality of trenches, and etching the doped layer.

[0034] According to still another embodiment of the present disclosure, in the method of manufacturing a power semiconductor device, each of the plurality of hole injection regions may have a lesser thickness than a thickness of the capping layer.

[0035] According to still another embodiment of the present disclosure, the method of manufacturing a power semiconductor device may further include: forming a gate electrode on the capping layer; forming a first field plate apart from the gate electrode; and forming a second field plate above and apart from the first field plate.

[0036] The present disclosure has the following effects by the above configurations.

[0037] According to the present disclosure, by forming a plurality of hole injection regions spaced apart from each other at the bottom of a drain electrode, it is possible to capture electrons trapped between a gate electrode and the drain electrode to prevent current collapse effects.

[0038] In addition, according to the present disclosure, by forming a plurality of protruding regions that protrude downward on the lower side of a drain electrode to be spaced apart, it is possible to increase the total area of a current path by increasing a junction area between GaN of a channel layer and a metal layer such as Ti of a drain electrode.

[0039] In addition, according to the present disclosure, by etching a barrier layer and a channel layer located in the space between hole injection regions, it is possible to ensure process uniformity.

[0040] In addition, according to the present disclosure, by forming a first field plate and/or a second field plate on the side spaced apart from a gate electrode, it is possible to reduce an electric field between the gate electrode and a drain electrode.

[0041] Furthermore, according to the present disclosure, by having a drain electrode form a wing portion, it is possible to reduce an electric field between a gate electrode and the drain electrode.

[0042] Meanwhile, it should be added that even if effects are not explicitly mentioned herein, the effects described in the following specification expected by the technical features of the present disclosure and their potential effects are treated as if they were described in the specification of the present disclosure.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0043] The above and other objectives, features, and other advantages of the present disclosure will be more clearly understood from the following detailed description when taken in conjunction with the accompanying drawings, in which:

[0044] FIG. 1 is a cross-sectional view of a conventional nitride-based power semiconductor device;

[0045] FIG. 2 is a cross-sectional view of a power semiconductor device according to an embodiment of the present disclosure;

[0046] FIG. 3 is a plan view showing a hole injection region according to a first embodiment of the present disclosure;

[0047] FIG. 4 is a plan view showing a hole injection region according to a second embodiment of the present disclosure; and

[0048] FIGS. 5 to 15 are cross-sectional views showing a method of manufacturing a power semiconductor device according to an embodiment of the present disclosure.

DETAILED DESCRIPTION OF THE INVENTION

[0049] Hereinafter, embodiments of the present disclosure will be described in more detail with reference to the accompanying drawings. The embodiments of the present disclosure may be modified in various forms, and the scope of the present disclosure should not be construed as being limited to the following embodiments, but should be construed based on the matters described in the claims. In addition, these embodiments are only provided for reference in order to more completely explain the present disclosure to those of ordinary skill in the art.

[0050] As used herein, the singular form may include the plural form unless the context clearly indicates otherwise. In addition, as used herein, “comprise” and/or “comprising” specify the presence of the recited shapes, numbers, steps, operations, members, elements, and/or groups thereof, but do not exclude the presence or addition of one or more other shapes, numbers, steps, operations, members, elements, and/or groups thereof.

[0051] Hereinafter, it should be noted that when one component (or layer) is described as being disposed on another component (or layer), one component may be disposed directly on another component, or another component(s) or layer(s) may be located between the components. In addition, when one component is expressed as being directly disposed on or above another component, no other component(s) are located between the components. Moreover, being located on “top”, “upper”, “lower”, “top”, “bottom” or “one (first) side” or “side” of a component means a relative positional relationship.

[0052] Terms such as first, second, etc. may be used to describe various items such as various elements, areas and/or parts, but the items are not limited by these terms.

[0053] In addition, it should be noted that, where certain embodiments are otherwise feasible, certain process sequences may be performed other than those described below. For example, two processes described in succession may be performed substantially simultaneously or in the reverse order.

[0054] Furthermore, the conductivity type or doped region of the components may be defined as “p-type” or “n-type” according to the main carrier characteristics, but this is only for convenience of description, and the technical spirit of the present disclosure is not limited to what is illustrated. For example, hereinafter, “p-type” or “n-type” will be used as more general terms “first conductivity type” or “second conductivity type”, and here, the first conductivity type means p-type, and the second conductivity type means n-type.

[0055] FIG. 2 is a cross-sectional view of a power semiconductor device according to an embodiment of the present disclosure.

[0056] Hereinafter, a power semiconductor device **1** according to an embodiment of the present disclosure will be described in detail with reference to the accompanying drawings. The above “power semiconductor device **1**” is understood to be a nitride-based power semiconductor device.

[0057] Referring to FIG. 2, the present disclosure relates to a power semiconductor device **1** and, more particularly, to a power semiconductor device **1** seeking to increase a current path area and to capture electrons trapped between a gate electrode and a drain electrode to prevent current collapse effects by forming a plurality of hole injection regions spaced apart from each other at the bottom of the drain electrode.

[0058] First, a substrate **101** may be formed in the power semiconductor device **1** according to an embodiment of the present disclosure. The substrate **101** is a substrate for growth, and may be, for example, a silicon substrate, but is not limited thereto, and may be, for example, a sapphire substrate, a GaN substrate, or a SiC substrate. In the present disclosure, it will be described as an example that the substrate **101** is a silicon substrate.

[0059] A buffer layer **110** may be formed on the substrate **101**. The buffer layer **110** may be formed, for example, by growing AlN to a predetermined thickness on the substrate **101**.

Alternatively, the buffer layer **110** may be a form in which one or more composite layers of GaN and AlGaIn are grown, but is not limited thereto. The buffer layer **110** may have a structure for

preventing stress caused by a difference in lattice constants and thermal expansion coefficients between the substrate **101** and a channel layer **120** to be described later. The buffer layer **110** may be doped with impurities such as C and/or Fe.

[0060] The channel layer **120** is formed on the substrate **101**, more preferably on the buffer layer **110**, and may include, for example, a nitride-based semiconductor layer such as GaN. A two-dimensional electron gas (2DEG) layer (not shown) may be formed on the side adjacent the interface between the channel layer **120** and the barrier layer **130**, which will be described later, and the 2DEG layer may be formed within the channel layer **120**.

[0061] The barrier layer **130** may be formed on the channel layer **120**. The barrier layer **130** is, for example, a nitride-based semiconductor layer such as AlGaN, and is preferably a nitride-based semiconductor layer that is different from the channel layer **120**. The density and mobility of the 2DEG layer may be controlled by adjusting the Al and Ga contents of the barrier layer **130**.

[0062] A passivation layer **140** may be formed on the barrier layer **130**. The passivation layer **140** may be, for example, an Al₂O₃ layer or a SiN layer, but there is no particular limitation thereon. In addition, it should be noted that the passivation layer **140** may be formed on the barrier layer **130** and to cover a capping layer **151**, which will be described later, but is not an essential component of the present disclosure.

[0063] The capping layer **151** may be formed on the barrier layer **130**. The capping layer **151** is formed on the barrier layer **130** and below a gate electrode **160**, and in some cases, may be covered by the passivation layer **140** under the gate electrode **160**. The capping layer **151** is, for example, an impurity doped region of the first conductivity type and preferably has positive polarity. When the capping layer **151** is formed to a predetermined thickness or more, the distance from the gate electrode **160** to the 2DEG layer becomes longer, which may reduce the response speed. On the contrary, when the capping layer **151** is formed to a predetermined thickness or less, it is difficult to achieve a normally-off operation. Thus, it is desirable that the capping layer **151** is formed to an appropriate thickness. As an example, the capping layer **151** may be formed by growing p-GaN, for example, by doping Mg into GaN, but the scope of the present disclosure is not limited thereto.

[0064] The capping layer **151** is formed at the bottom of the gate electrode **160**, so that the 2DEG layer does not exist under the capping layer **151** during non-operation. Thus, since the 2DEG layer does not exist in the channel layer **120** when the gate voltage is off, the device operates in a normally-off fashion, and when the gate voltage is turned on, the 2DEG layer is formed and the device is driven. In addition, the capping layer **151** may be deposited on the barrier layer **130** in the same process as a hole injection region **153**, and a detailed description thereof will be provided later.

[0065] The gate electrode **160** may be formed on the barrier layer **130**. The gate electrode **160** is formed on the barrier layer **130**, for example, on the capping layer **151**, and may be formed of a single layer or a composite layer of various arbitrary metals such as Al, Ti, Pd, etc. In addition, the gate electrode **160** operates normally off, and a depletion layer of the gate electrode **160** passes through the barrier layer **130** to reach the channel layer **120** and blocks the 2DEG layer.

[0066] A source electrode **171** and a drain electrode **173** may be formed spaced apart from the gate electrode **160**. The source electrode **171** and the drain electrode **173** are ohmic contact regions formed on the barrier layer **130**. It should be noted that the source electrode **171** and the drain electrode **173** may be formed in, for example, a stepped cross-sectional shape or a rectangular cross-sectional shape, but may be formed in various other structures. As an example, the source electrode **171** and the drain electrode **173** may be formed in a structure in which at least one side thereof is stepped along the horizontal direction, and the same applies to the gate electrode **160**. The source electrode **171**, the gate electrode **160**, and the drain electrode **173** may be sequentially spaced apart from each other along the horizontal direction. In addition, the source electrode **171** and the drain electrode **173** may be made of, for example, a single layer or a composite layer of various arbitrary metals capable of ohmic contact, such as Ti, Au, and Al, and there is no particular

limitation thereon.

[0067] At this time, the drain electrode **173** may include a wing portion **1731** that protrudes by a predetermined length to a side adjacent to the gate electrode **160** along the lateral direction at a predetermined height. That is, the wing portion **1731** extends laterally from a predetermined height of the drain electrode **173** toward the gate electrode **160**, and an insulating film **180** may be formed under the wing portion **1731**. The wing portion **1731** may function as a drain field plate to reduce an electric field between the gate electrode **160** and the drain electrode **173**.

[0068] In addition, the lower ends of the source electrode **171** and/or the drain electrode **173** may be located on the barrier layer **130** or may be located directly above the channel layer **120**. For example, when the source electrode **171** and/or the drain electrode **173** are located directly above the channel layer **120**, the barrier layer **130** on the side where the lower ends of the source electrode **171** and/or the drain electrode **173** will be formed is removed, and the channel layer **120** immediately below the barrier layer **130** may also be partially removed. That is, the channel layer **120** may have a recess region **121**.

[0069] In an embodiment of the present disclosure, one or more protruding regions **1733** may be formed laterally at the bottom of the drain electrode **173**, preferably spaced apart from each other to form a plurality of protruding regions **1733**. The protruding region **1733** may have a structure that protrudes downward from the bottom of the drain electrode **173**. The hole injection region **153** and the channel layer **120** may be positioned from top to bottom on one side where the protruding region **1733** makes contact. In addition, the hole injection region **153**, the barrier layer **130**, and the channel layer **120** on the side where the protruding region **1733** is formed may be removed. In this case, the height of the channel layer **120** immediately below the protruding region **1733** is lower than that of the channel layer **120** on the side where the protruding region **1733** is not formed. That is, the recess region **121** may be formed.

[0070] In this way, when the drain electrode **173** has multiple protruding regions **1733**, a junction area between GaN of the channel layer **120** and a metal layer such as Ti of the drain electrode **173** may be increased compared to a conventional structure, which may increase the overall current path area of the semiconductor device **1**.

[0071] The insulating film **180** may be formed to cover the gate electrode **160**, the source electrode **171**, and the drain electrode **173**. The insulating film **180** may be formed as a multilayer structure and may have a structure including an oxide film, a nitride film, or both an oxide film and a nitride film, but there is no particular limitation thereon.

[0072] In addition, a first field plate **191** and a second field plate **193** may be formed within or on the insulating film **180** on a side spaced apart from the gate electrode **160**. As an example, the first field plate **191** may be formed between the gate electrode **160** and the drain electrode **173**, and the second field plate **193** may be formed above the first field plate **191** and spaced apart from the first field plate **191**, but there is no particular limitation thereon. The first field plate **191** is a layer containing a conductive material and may be electrically connected to the gate electrode **160**. The second field plate **193** is also a layer containing a conductive material and may be electrically connected to the source electrode **171**. Both the first field plate **191** and the second field plate **193** may perform the function of reducing the electric field between the gate electrode **160** and the drain electrode **173**, but it should be noted that the first field plate **191** and the second field plate **193** are not essential components of the present disclosure.

[0073] As previously described, the hole injection region **153** may be formed on the side that contacts at least one side of the adjacent protruding region **1733** of the drain electrode **173**. A plurality of hole injection regions **153** may be formed to be spaced apart from each other along the lateral direction. The hole injection regions **153**, like the capping layer **151**, may be formed by growing p-GaN. That is, the hole injection regions **153** may include the same material as the capping layer **151**, but the scope of the present disclosure is not limited thereto.

[0074] Below, before explaining the features of the present disclosure, the problems of a

conventional power semiconductor device **9** will be described in detail.

[0075] Referring to FIG. **1**, in the conventional power semiconductor device **9**, a higher voltage than the voltage applied to a source electrode **910** and a gate electrode **930** may be applied to a drain electrode **950**. In this case, carriers may be trapped between the gate electrode **930** and the drain electrode **950**. Due to the carrier trapping, a current collapse phenomenon occurs, and this current collapse may cause a “memory effect” in which conduction current of a device may vary depending on how long a previously applied voltage has been present. For example, during transistor operation, electrons are trapped in an epitaxial layer or a dielectric layer, and at this time, the trapped electrons may repel electrons traveling through a channel, impeding current conduction through a 2DEG layer **970**. This may immediately cause a problem of increasing the resistance of the channel.

[0076] Referring to FIG. **2**, in order to solve the above-described problem, in an embodiment of the present disclosure, the hole injection regions **153** are formed laterally spaced apart from each other on the drain electrode **173** side. To be specific, the hole injection regions **153** may inject holes to capture electrons trapped on the side adjacent to the barrier layer **130**. That is, the hole injection regions **153** inject holes into a channel to allow the holes to combine with trapped electrons, thereby lowering the electrical resistance of the device and minimizing the memory effect. In addition, the hole injection region **153** may have a lesser top and bottom thickness than the capping layer **151** or may have substantially the same thickness.

[0077] FIG. **3** is a plan view showing a hole injection region according to a first embodiment of the present disclosure. For convenience of explanation, the insulating film and the drain electrode on the barrier layer are deleted in the attached FIG. **3**.

[0078] Referring to FIG. **3**, in the first embodiment, the hole injection region **153** may be provided in the form of multiple islands. When the hole injection region **153** is formed in this form, a junction area between GaN of the channel layer **120** and a metal layer such as Ti of the drain electrode **173** may be further increased.

[0079] FIG. **4** is a plan view showing a hole injection region according to a second embodiment of the present disclosure. For convenience of explanation, the insulating film and the drain electrode on the barrier layer are deleted in the attached FIG. **4**.

[0080] Referring to FIG. **4**, in the second embodiment, the hole injection region **253** may be provided in the form of multiple stripes spaced apart from each other along the lateral direction. Even in this case, a junction area between GaN of the channel layer **220** and a metal layer such as Ti of the drain electrode **173** may be increased.

[0081] FIGS. **5** to **15** are cross-sectional views showing a method of manufacturing a power semiconductor device according to an embodiment of the present disclosure.

[0082] Hereinafter, the method of manufacturing a power semiconductor device according to an embodiment of the present disclosure will be described in detail with reference to the attached drawings.

[0083] First, referring to FIG. **5**, a buffer layer **110**, a channel layer **120**, and a barrier layer **130** are sequentially formed on a substrate **101**. As previously described, the substrate **101** is a growth substrate and may be any one of a silicon substrate, a sapphire substrate, a GaN substrate, and a SiC substrate. However, in the present disclosure, the silicon substrate is used as an example. The buffer layer **110** may be formed on the substrate **101** and under the channel layer **120** by, for example, growing an AlN layer to a predetermined thickness. In addition, the channel layer **120** on the buffer layer **110** may be a nitride-based semiconductor layer such as GaN, and the barrier layer **130** on the channel layer **120** may be a semiconductor layer such as AlGaIn.

[0084] A 2DEG layer (not shown) may be formed by electrons accumulating at the interface of the channel layer **120** and the barrier layer **130**. To be specific, piezo polarization may occur at the interface between the channel layer **120** and the barrier layer **130** due to the difference in lattice constants between GaN and AlGaIn. At this time, the piezo polarization and spontaneous

polarization of the channel layer **120** and the barrier layer **130** work, and a two-dimensional electron gas with a high electron concentration may be generated at the interface of both components.

[0085] Thereafter, a capping layer **151** and a doped region **155**, which is a previous stage of the hole injection region **153**, may be formed on the barrier layer **130**. For example, referring to FIG. **6**, a doped layer **D1** formed by growing GaN of the first conductivity type is formed on the barrier layer **130**. Then, referring to FIGS. **6** and **7**, the capping layer **151** and the doped region **155** may be formed by etching the doped layer **D1** using a mask pattern **M1**. A plurality of doped regions **155** may be formed to be spaced apart from each other along the lateral direction.

[0086] Thereafter, referring to FIG. **8**, a first insulating film layer **I1** may be formed to cover the capping layer **151** and the doped region **155**. The first insulating film layer **I1** may be formed as a multilayer film including a passivation layer **140**, but the scope of the present disclosure is not limited thereto.

[0087] Thereafter, the first insulating layer **I1** on the side where a source electrode **171** and a drain electrode **173** will be formed is removed or etched. For example, referring to FIG. **9**, a mask pattern **M2** may be formed on the first insulating film layer **I1**, and the first insulating film layer **I1** on the side where the source electrode **171** and the drain electrode **173** will be formed may be removed. Due to this, the doped region **155** may be opened. Through this process, openings **O1** and **O2** may be formed on the side where the source electrode **171** and the drain electrode **173** are to be formed.

[0088] Thereafter, referring to FIG. **10**, the barrier layer **130** and the channel layer **120** on the openings **O1** and **O2** sides are removed. To be specific, the barrier layer **130** of the opening **O1** side where the source electrode **171** is formed may be removed, and the channel layer **120** may be removed to a predetermined thickness. In addition, the barrier layer **130** of the opening **O2** side where the drain electrode **173** is formed may be removed, and the channel layer **120** may be removed to a predetermined thickness. A recess region **121** may be formed through this process. At this time, the barrier layer **130** and the channel layer **120** removed from the opening **O2** side may be regions that do not overlap the doped region **155**. In addition, in this process, the doped region **155** may also be removed to a predetermined thickness. Thus, the thickness of the doped region **155** is lesser than that of the capping layer **151**, so that the hole injection region **153** may be completed. At this time, the existing second mask pattern **M2** may be used. However, it should be noted that this process is not an essential step of the present disclosure.

[0089] Thereafter, the source electrode **171** and the drain electrode **173** may be formed. To illustratively explain this with reference to FIG. **11**, a first conductive layer (not shown) is formed to fill the openings **O1** and **O2** and on the first insulating film layer **I1**. Then, the first conductive layer may be removed using a mask pattern (not shown) on the first conductive layer (not shown) to form the source electrode **171** and the drain electrode **173**.

[0090] Thereafter, a second insulating film layer **I2** may be formed on the first insulating film layer **I1** to cover the source electrode **171** and the drain electrode **173**. The second insulating film layer **I2** may include the same material as the first insulating layer **I1**, or may include a different material.

[0091] Thereafter, a gate electrode **160** may be formed by partially removing the first insulating film layer **I1** and the second insulating film layer **I2**. For example, referring to FIGS. **12** and **13**, a second conductive layer (not shown) is formed on the second insulating film layer **I2**. Then, the second conductive layer may be removed using a mask pattern (not shown) on the second conductive layer to form the gate electrode **160**. At this time, a first field plate **191** may also be formed on a side spaced apart from the gate electrode **160**.

[0092] Thereafter, referring to FIG. **14**, a third insulating film layer **I3** may be formed on the second insulating film layer **I2** to cover the gate electrode **160** and the first field plate **191**.

[0093] Finally, referring to FIG. **15**, a second field plate **193** may be formed on the third insulating film layer **I3**. The second field plate **193** may be formed by forming a third conductive layer (not shown) on the third insulating film layer **I3** and then removing the third conductive layer using a

mask pattern (not shown).

[0094] The above detailed description is illustrative of the present disclosure. In addition, the above description shows and describes preferred embodiments of the present disclosure, and the present disclosure can be used in various other combinations, modifications, and environments. That is, changes or modifications are possible within the scope of the concept of the disclosure disclosed herein, the scope equivalent to the written disclosure, and/or within the scope of skill or knowledge in the art. The above-described embodiment describes the best state for implementing the technical idea of the present disclosure, and various changes required in the specific application field and use of the present disclosure are possible. Accordingly, the detailed description of the present disclosure is not intended to limit the present disclosure to the disclosed embodiments.

Claims

1. A power semiconductor device, comprising: a substrate; a channel layer having a first nitride-based semiconductor layer and disposed on the substrate; a barrier layer disposed on the channel layer and having a second nitride-based semiconductor layer that is different from the first nitride-based semiconductor layer of the channel layer; a capping layer having an impurity doped region of a first conductivity type and disposed on the barrier layer; a gate electrode disposed on the capping layer; a plurality of hole injection regions, each having an impurity doped region of a first conductivity type, each being laterally spaced apart from another on the barrier layer; and a drain electrode in contact with the plurality of hole injection regions.
2. The power semiconductor device of claim 1, wherein the drain electrode comprises a plurality of protruding regions, each being disposed at a bottom of the drain electrode in a space between the plurality of hole injection regions.
3. The power semiconductor device of claim 2, wherein the plurality of protruding regions have bottoms thereof extending into the channel layer.
4. The power semiconductor device of claim 2, wherein an upper surface of the channel layer below each of the plurality of hole injection regions is disposed at a higher position than an upper surface of the channel layer below each of the plurality of protruding regions.
5. The power semiconductor device of claim 2, wherein the capping layer has a greater top to bottom thickness compared to a top to bottom thickness of each of the plurality of hole injection regions.
6. The power semiconductor device of claim 2, wherein the plurality of hole injection regions are spaced apart from each other in an island pattern.
7. The power semiconductor device of claim 2, wherein the plurality of hole injection regions are laterally spaced from each other in a stripe pattern.
8. The power semiconductor device of claim 2, wherein the drain electrode further comprises a wing portion that protrudes a predetermined length from a predetermined height of the drain electrode toward a side adjacent to the gate electrode.
9. The power semiconductor device of claim 2, further comprising: an insulating film covering the gate electrode and the drain electrode; and a first field plate disposed apart from the gate electrode within the insulating film, wherein the first field plate is electrically connected to the gate electrode.
10. The power semiconductor device of claim 2, further comprising: a source electrode disposed apart from the gate electrode; and a second field plate disposed apart from the gate electrode within an insulating film, wherein the second field plate is electrically connected to the source electrode.
11. A power semiconductor device, comprising: a substrate; a channel layer having a first nitride-based semiconductor layer and disposed on the substrate; a barrier layer disposed on the channel layer and having a second nitride-based semiconductor layer that is different from the first nitride-based semiconductor layer of the channel layer; a capping layer having an impurity doped region of

a first conductivity type and disposed on the barrier layer; a gate electrode disposed on the capping layer; a plurality of hole injection regions, each having an impurity doped region of a first conductivity type and laterally disposed apart from another on the barrier layer; a source electrode disposed apart from the gate electrode; and a drain electrode disposed apart from the gate electrode and including a plurality of protruding regions, each being disposed in a space between the plurality of hole injection regions.

12. The power semiconductor device of claim 11, wherein the capping layer has a thickness that is substantially the same as a thickness of each of the plurality of hole injection regions.

13. The power semiconductor device of claim 11, further comprising: an insulating film covering the gate electrode, the source electrode, and the drain electrode; a first field plate disposed apart from the gate electrode within the insulating film; and a second field plate disposed apart from the first field plate within the insulating film, wherein the first field plate is electrically connected to the gate electrode and the second field plate is electrically connected to the source electrode.

14. The power semiconductor device of claim 11, wherein each of the plurality of protruding regions has a longer vertical length than a vertical length of each of the plurality of hole injection regions adjacent thereto.

15. A method of manufacturing a power semiconductor device, the method comprising: forming a channel layer having a first nitride-based semiconductor layer on a substrate; forming a barrier layer having a second nitride-based semiconductor layer that is different from the first nitride-based semiconductor layer on the channel layer; forming a capping layer of a first conductivity type on the barrier layer; forming a plurality of hole injection regions on the barrier layer apart from the capping layer; forming a first insulating film layer on the barrier layer to cover the capping layer and the plurality of hole injection regions; and forming a source electrode and a drain electrode after etching the first insulating film layer.

16. The method of claim 15, wherein the plurality of hole injection regions are provided to be spaced apart from each other by forming a first doped layer on the barrier layer and then etching the first doped layer using a mask pattern.

17. The method of claim 16, wherein the drain electrode is provided by: forming a plurality of trenches by etching the barrier layer and the channel layer beneath a plurality of spaces separating the plurality of hole injection regions from each other, forming a doped layer of a first conductivity type to cover the plurality of hole injection regions and fill the plurality of trenches, and etching the doped layer.

18. The method of claim 16, wherein each of the plurality of hole injection regions has a lesser thickness than a thickness of the capping layer.

19. The method of claim 16, further comprising: forming a gate electrode on the capping layer; forming a first field plate apart from the gate electrode; and forming a second field plate above and apart from the first field plate.
