

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250280730

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

KWON; Soonhyung et al.

COMPOSITION FOR ORGANIC OPTOELECTRONIC DEVICE, ORGANIC OPTOELECTRONIC DEVICE, AND DISPLAY DEVICE

Abstract

A composition for an organic optoelectronic device, an organic optoelectronic device including the same, and a display device, the composition for an organic optoelectronic device including a first compound represented by Chemical Formula 1 and a second compound represented by Chemical Formula 2,

##STR00001##

Inventors: KWON; Soonhyung (Suwon-si, KR), AN; Eunhye (Suwon-si, KR), KANG; Giwook (Suwon-si, KR), CHOI; Eunjeong (Suwon-si, KR), JANG; Dongjin (Suwon-si, KR), KIM; Dosik (Suwon-si, KR), SHIN; Jisoo (Suwon-si, KR)

Applicant: SAMSUNG SDI CO., LTD. (Yongin-si, KR)

Family ID: 96880825

Appl. No.: 19/062218

Filed: February 25, 2025

Foreign Application Priority Data

KR

10-2024-0030867

Mar. 04, 2024

Publication Classification

Int. Cl.: H10K85/60 (20230101); C09K11/02 (20060101); C09K11/06 (20060101); H10K50/12 (20230101); H10K50/15 (20230101); H10K85/30 (20230101)

U.S. Cl.:

CPC H10K85/6572 (20230201); C09K11/02 (20130101); C09K11/06 (20130101); H10K85/346 (20230201); H10K85/654 (20230201); H10K85/658 (20230201);

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2024-0030867 filed in the Korean Intellectual Property Office on Mar. 4, 2024, the entire contents of which are incorporated herein by reference.

BACKGROUND

1. Field

[0002] Embodiments relate to a composition for an organic optoelectronic device, an organic optoelectronic device, and a display device.

2. Description of the Related Art

[0003] An organic optoelectronic device (e.g., an organic optoelectronic diode) is a device capable of converting electrical energy and optical energy to each other.

[0004] Organic optoelectronic devices may be divided into two types according to a principle of operation. One is a photoelectric device that generates electrical energy by separating excitons formed by light energy into electrons and holes, and transferring the electrons and holes to different electrodes, respectively and the other is a light emitting device that generates light energy from electrical energy by supplying voltage or current to the electrodes.

[0005] Examples of the organic optoelectronic device may include an organic photoelectric device, an organic light emitting diode, an organic solar cell, and an organic photoconductor drum.

[0006] Among them, organic light emitting diodes (OLEDs) are attracting much attention in recent years due to increasing demands for flat panel display devices. The organic light emitting diode may be a device that converts electrical energy into light, and the performance of the organic light emitting diode may be greatly influenced by an organic material between electrodes.

SUMMARY

[0007] The embodiments may be realized by providing a composition for an organic optoelectronic device, the composition including a first compound represented by Chemical Formula 1; and a second compound represented by Chemical Formula 2:

##STR00002## [0008] wherein, in Chemical Formula 1, Z^{sup.1} to Z^{sup.3} are each independently N or CR^{sup.a}, wherein R^{sup.a} is hydrogen, deuterium, a substituted or unsubstituted C1 to C20 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, a cyano group, or a halogen, provided that at least two of Z^{sup.1} to Z^{sup.3} are N, L^{sup.1} to L^{sup.3} are each independently a single bond, a substituted or unsubstituted C6 to C20 arylene group, or a substituted or unsubstituted divalent C2 to C20 heterocyclic group, and Ar^{sup.1} to Ar^{sup.3} are each independently a substituted or unsubstituted C6 to C30 aryl group or a substituted or unsubstituted C2 to C30 heterocyclic group, provided that at least one of Ar^{sup.1} to Ar^{sup.3} is a group represented by Chemical Formula A,

##STR00003## [0009] wherein, in Chemical Formula A, R^{sup.1} to R^{sup.11} are each independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, a substituted or unsubstituted amine group, a substituted or unsubstituted silyl group, a cyano group, a halogen or a linking point with Chemical Formula 1, and R^{sup.1} to R^{sup.11} are separately present or two adjacent ones of R^{sup.1} to R^{sup.11} are linked to each other to form a ring,

##STR00004## [0010] wherein, in Chemical Formula 2, L^{sup.7} and L^{sup.8} are each

independently a single bond or a substituted or unsubstituted C6 to C30 arylene group, Ar.sup.7 is a substituted or unsubstituted C6 to C30 aryl group or a substituted or unsubstituted C2 to C30 heterocyclic group, and R.sup.30 to R.sup.33, R.sup.34', R.sup.34'', R.sup.34''', and R.sup.35 to R.sup.42 are each independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, a substituted or unsubstituted amine group, a substituted or unsubstituted silyl group, a cyano group, or a halogen.

[0011] The embodiments may be realized by providing an organic optoelectronic device including an anode and a cathode facing each other, and a light emitting layer between the anode and the cathode, wherein the light emitting layer includes the composition for an organic optoelectronic device according to an embodiment.

[0012] The embodiments may be realized by a display device including the organic optoelectronic device according to an embodiment.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0013] Features will become apparent to those of skill in the art by describing in detail exemplary embodiments with reference to the attached drawings in which:

[0014] FIG. 1 is a cross-sectional view showing an example of an organic light emitting diode according to some embodiments, and

[0015] FIG. 2 is a cross-sectional view showing another example of an organic light emitting diode according to some embodiments.

DETAILED DESCRIPTION

[0016] Example embodiments will now be described more fully hereinafter with reference to the accompanying drawings; however, they may be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey exemplary implementations to those skilled in the art.

[0017] In the drawing figures, the dimensions of layers and regions may be exaggerated for clarity of illustration. It will also be understood that when a layer or element is referred to as being “on” another layer or substrate, it can be directly on the other layer or substrate, or intervening layers may also be present. Further, it will be understood that when a layer is referred to as being “under” another layer, it can be directly under, and one or more intervening layers may also be present. In addition, it will also be understood that when a layer is referred to as being “between” two layers, it can be the only layer between the two layers, or one or more intervening layers may also be present. Like reference numerals refer to like elements throughout.

[0018] As used herein, when a definition is not otherwise provided, “substituted” refers to replacement of at least one hydrogen of a substituent or a compound by deuterium, a halogen, a hydroxyl group, an amino group, a substituted or unsubstituted C1 to C30 amine group, a nitro group, a substituted or unsubstituted C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C6 to C30 arylsilyl group, a C3 to C30 cycloalkyl group, a C3 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a C1 to C10 trifluoroalkyl group, a cyano group, or a combination thereof.

[0019] In an implementation, the “substituted” refers to replacement of at least one hydrogen of a substituent or a compound by deuterium, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C6 to C30 arylsilyl group, a C3 to C30 cycloalkyl group, a C3 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, or a cyano group. In an implementation, the “substituted” refers to replacement of at least one hydrogen of a substituent or a compound by

deuterium, a C1 to C20 alkyl group, a C6 to C30 aryl group, or a cyano group. In an implementation, the “substituted” refers to replacement of at least one hydrogen of a substituent or a compound by deuterium, a C1 to C5 alkyl group, a C6 to C18 aryl group, or a cyano group. In an implementation, the “substituted” refers to replacement of at least one hydrogen of a substituent or a compound by deuterium, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group.

[0020] “Unsubstituted” refers to non-replacement of a hydrogen atom by another substituent and remaining of the hydrogen atom.

[0021] In the present specification, “hydrogen substitution (—H)” may include “deuterium substitution (—D)” or “tritium substitution (—T).” For example, any hydrogen in any compound described herein may be protium, deuterium, or tritium (e.g., based on natural or artificial substitution).

[0022] As used herein, when a definition is not otherwise provided, “hetero” refers to one including one to three heteroatoms selected from N, O, S, P, and Si, and remaining carbons in one functional group.

[0023] As used herein, “aryl group” refers to a group including at least one hydrocarbon aromatic moiety, and all elements of the hydrocarbon aromatic moiety have p-orbitals which form conjugation, for example a phenyl group, a naphthyl group, and the like, two or more hydrocarbon aromatic moieties may be linked by a sigma bond and may be, for example a biphenyl group, a terphenyl group, a quaterphenyl group, and the like, and two or more hydrocarbon aromatic moieties are fused directly or indirectly to provide a non-aromatic fused ring, for example a fluorenyl group.

[0024] The aryl group may include a monocyclic, polycyclic, or fused ring polycyclic (i.e., rings sharing adjacent pairs of carbon atoms) functional group.

[0025] As used herein, “heterocyclic group” is a generic concept of a heteroaryl group, and may include at least one heteroatom selected from N, O, S, P, and Si instead of carbon (C) in a cyclic compound such as aryl group, a cycloalkyl group, a fused ring thereof, or a combination thereof. When the heterocyclic group is a fused ring, the entire ring or each ring of the heterocyclic group may include one or more heteroatoms.

[0026] As an example, “heteroaryl group” may refer to an aryl group including at least one heteroatom selected from N, O, S, P, and Si. Two or more heteroaryl groups are linked by a sigma bond directly, or when the heteroaryl group includes two or more rings, the two or more rings may be fused. When the heteroaryl group is a fused ring, each ring may include one to three heteroatoms.

[0027] More specifically, the substituted or unsubstituted C6 to C30 aryl group may be a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted anthracenyl group, a substituted or unsubstituted phenanthrenyl group, a substituted or unsubstituted naphthacenyl group, a substituted or unsubstituted pyrenyl group, a substituted or unsubstituted biphenyl group, a substituted or unsubstituted p-terphenyl group, a substituted or unsubstituted m-terphenyl group, a substituted or unsubstituted o-terphenyl group, a substituted or unsubstituted chrysenyl group, a substituted or unsubstituted triphenylene group, a substituted or unsubstituted perylenyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted indenyl group, or a combination thereof.

[0028] More specifically, the substituted or unsubstituted C2 to C30 heterocyclic group may be substituted or unsubstituted furanyl group, a substituted or unsubstituted thiophenyl group, a substituted or unsubstituted pyrrolyl group, a substituted or unsubstituted pyrazolyl group, a substituted or unsubstituted imidazolyl group, a substituted or unsubstituted triazolyl group, a substituted or unsubstituted oxazolyl group, a substituted or unsubstituted thiazolyl group, a substituted or unsubstituted oxadiazolyl group, a substituted or unsubstituted thiadiazolyl group, a substituted or unsubstituted pyridyl group, a substituted or unsubstituted pyrimidinyl group, a

substituted or unsubstituted pyrazinyl group, a substituted or unsubstituted triazinyl group, a substituted or unsubstituted benzofuranyl group, a substituted or unsubstituted benzothiophenyl group, a substituted or unsubstituted benzimidazolyl group, a substituted or unsubstituted indolyl group, a substituted or unsubstituted quinolinyl group, a substituted or unsubstituted isoquinolinyl group, a substituted or unsubstituted quinazolinyl group, a substituted or unsubstituted quinoxalinyl group, a substituted or unsubstituted naphthyridinyl group, a substituted or unsubstituted benzoxazinyl group, a substituted or unsubstituted benzthiazinyl group, a substituted or unsubstituted acridinyl group, a substituted or unsubstituted phenazinyl group, a substituted or unsubstituted phenothiazinyl group, a substituted or unsubstituted phenoxazinyl group, a substituted or unsubstituted carbazolyl group, a substituted or unsubstituted dibenzofuranyl group, a substituted or unsubstituted dibenzothiophenyl group, or a combination thereof.

[0029] As used herein, hole characteristics refer to an ability to donate an electron to form a hole when an electric field is applied and that a hole formed in the anode may be easily injected into the light emitting layer and transported in the light emitting layer due to conductive characteristics according to a highest occupied molecular orbital (HOMO) level.

[0030] In addition, electronic characteristics refer to an ability to accept an electron when an electric field is applied and that electron formed in the cathode may be easily injected into the light emitting layer and transported in the light emitting layer due to conductive characteristics according to a lowest unoccupied molecular orbital (LUMO) level.

[0031] Hereinafter, a composition for an organic optoelectronic device according to some embodiments will be described.

[0032] The composition for an organic optoelectronic device according to some embodiments may include, e.g., a first compound represented by Chemical Formula 1 and a second compound represented by Chemical Formula 2.

##STR00005##

[0033] In Chemical Formula 1, Z^{sup.1} to Z^{sup.3} may each independently be, e.g., N or CR^{sup.a}, wherein R^{sup.a} may be or include, e.g., hydrogen, deuterium, a substituted or unsubstituted C1 to C20 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, a cyano group, or a halogen.

[0034] In an implementation, at least two of Z^{sup.1} to Z^{sup.3} are N.

[0035] L^{sup.1} to L^{sup.3} may each independently be or include, e.g., a single bond, a substituted or unsubstituted C6 to C20 arylene group, or a substituted or unsubstituted divalent C2 to C20 heterocyclic group.

[0036] Ar^{sup.1} to Ar^{sup.3} may each independently be or include, e.g., a substituted or unsubstituted C6 to C30 aryl group or a substituted or unsubstituted C2 to C30 heterocyclic group, provided that at least one of Ar^{sup.1} to Ar^{sup.3} is a group represented by Chemical Formula A.

##STR00006##

[0037] In Chemical Formula A, R^{sup.1} to R^{sup.11} may each independently be or include, e.g., hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, a substituted or unsubstituted amine group, a substituted or unsubstituted silyl group, a cyano group, a halogen or a linking point with Chemical Formula 1.

[0038] R^{sup.1} to R^{sup.11} may be separately present or two adjacent ones of R^{sup.1} to R^{sup.11} may be linked to each other to form a ring.

##STR00007##

[0039] In Chemical Formula 2, L^{sup.7} and L^{sup.8} may each independently be or include, e.g., a single bond or a substituted or unsubstituted C6 to C30 arylene group.

[0040] Ar^{sup.7} may be or include, e.g., a substituted or unsubstituted C6 to C30 aryl group or a substituted or unsubstituted C2 to C30 heterocyclic group.

[0041] R^{sup.30} to R^{sup.33}, R^{sup.34'}, R^{sup.34''}, R^{sup.34'''}, and R^{sup.35} to R^{sup.42} may each

independently be or include, e.g., hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, a substituted or unsubstituted amine group, a substituted or unsubstituted silyl group, a cyano group, or a halogen.

[0042] The first compound and the second compound may be bipolar compounds having both electronic characteristics and hole characteristics, respectively. The first compound may be a bipolar compound with relatively strong electronic characteristics, and the second compound may be a bipolar compound with relatively strong hole characteristics. In an implementation, the first compound and the second compound may exhibit good interfacial characteristics due to their structures.

[0043] The composition for an organic optoelectronic device may include the first compound and the second compound together to finely control the mobility of holes and electrons to balance holes and electrons in the active layer (e.g., light emitting layer) of the organic optoelectronic device.

[0044] In an implementation, the composition for an organic optoelectronic device may be used as a host for a light emitting layer, and may have good electrical matching with a blue light-emitting dopant that emits light in a blue emission spectrum described below, thereby increasing efficiency of the organic optoelectronic device and suppressing deterioration of the organic optoelectronic device. In an implementation, at least one of the first compound and the second compound may have a high triplet energy level of greater than or equal to about 2.8 eV, so that exciton transfer to the blue light-emitting dopant may be facilitated, thereby implementing an organic optoelectronic device having high efficiency and long life-span.

[0045] In an implementation, Z^{sup.1} to Z^{sup.3} in Chemical Formula 1 may each be, e.g., N.

[0046] In an implementation, Z^{sup.1} and Z^{sup.2} in Chemical Formula 1 may each be, e.g., N, and Z^{sup.3} may be CR^{sup.a}.

[0047] In an implementation, Z^{sup.1} and Z^{sup.3} in Chemical Formula 1 may each be, e.g., N, and Z^{sup.2} may be CR^{sup.a}.

[0048] In an implementation, Z^{sup.2} and Z^{sup.3} in Chemical Formula 1 may each be, e.g., Z^{sup.1} may be CR^{sup.a}.

[0049] In an implementation, L^{sup.1} to L^{sup.3} in Chemical Formula 1 may each independently be, e.g., a single bond, a substituted or unsubstituted phenylene group, a substituted or unsubstituted biphenylene group, a substituted or unsubstituted terphenylene group or a substituted or unsubstituted naphthylene group, a substituted or unsubstituted benzofuranylene group, a substituted or unsubstituted dibenzofuranylene group, a substituted or unsubstituted benzothiophenylene group, a substituted or unsubstituted dibenzothiophenylene group, or a substituted or unsubstituted fluorenylene group.

[0050] In an implementation, L^{sup.1} to L^{sup.3} in Chemical Formula 1 may each independently be, e.g., a single bond or a substituted or unsubstituted C6 to C20 arylene group, or may each independently be, e.g., a single bond or a substituted or unsubstituted phenylene group, a substituted or unsubstituted biphenylene group, a substituted or unsubstituted terphenylene group, or a substituted or unsubstituted naphthylene group.

[0051] In an implementation, L^{sup.1} to L^{sup.3} in Chemical Formula 1 may each be, e.g., a single bond.

[0052] In an implementation, one of Ar^{sup.1} to Ar^{sup.3} in Chemical Formula 1 may be, e.g., a group represented by Chemical Formula A. In an implementation, any two of Ar^{sup.1} to Ar^{sup.3} in Chemical Formula 1 may be, e.g., a group represented by Chemical Formula A. In an implementation, one of Ar^{sup.1} to Ar^{sup.3} in Chemical Formula 1 may be, e.g., a group represented by Chemical Formula A.

[0053] In an implementation, at least one of Ar^{sup.1} to Ar^{sup.3} in Chemical Formula 1 may be, e.g., a group represented by Chemical Formula A, and at least one of Ar^{sup.1} to Ar^{sup.3} in Chemical Formula 1 may be, e.g., a substituted or unsubstituted C6 to C30 aryl group or a

substituted or unsubstituted carbazolyl group. In an implementation, at least one of Ar.sup.1 to Ar.sup.3 in Chemical Formula 1 may be, e.g., substituted, e.g., with deuterium, a C6 to C30 aryl group, a cyano group, a halogen, or a combination thereof.

[0054] In an implementation, one of Ar.sup.1 to Ar.sup.3 in Chemical Formula 1 may be, e.g., a group represented by Chemical Formula 1 A, and the other two of Ar.sup.1 to Ar.sup.3 in Chemical Formula 1 may each independently be, e.g., a substituted or unsubstituted C6 to C30 aryl group or a substituted or unsubstituted carbazolyl group. In an implementation, at least one of Ar.sup.1 to Ar.sup.3 in Chemical Formula 1 may be substituted, e.g., with deuterium, a C6 to C30 aryl group, a cyano group, a halogen, or a combination thereof.

[0055] In an implementation, one of Ar.sup.1 to Ar.sup.3 in Chemical Formula 1 may be, e.g., a substituted or unsubstituted C6 to C30 aryl group or a substituted or unsubstituted carbazolyl group, and the other two of Ar.sup.1 to Ar.sup.3 in Chemical Formula 1 may each be, e.g., a group represented by Chemical Formula A. In an implementation, at least one of Ar.sup.1 to Ar.sup.3 in Chemical Formula 1 may be substituted, e.g., with deuterium, a C6 to C30 aryl group, a cyano group, a halogen, or a combination thereof.

[0056] In an implementation, one of R.sup.8 to R.sup.11 in Chemical Formula A may be a linking point with Chemical Formula 1.

[0057] In an implementation, one of R.sup.1 to R.sup.7 in Chemical Formula A may be a linking point with Chemical Formula 1.

[0058] In an implementation, the first compound may be, e.g., represented by one of Chemical Formulae 1A to 1C.

##STR00008##

[0059] In Chemical Formulae 1A to 1C, Z.sup.1 to Z.sup.3 and L.sup.1 to L.sup.3 may be defined the same as those of Chemical Formula 1.

[0060] Ar.sup.1 may be a group represented by, e.g., Chemical Formula A.

[0061] R.sup.12 to R.sup.27 may each independently be, e.g., hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, a substituted or unsubstituted amine group, a substituted or unsubstituted silyl group, a cyano group, or a halogen.

[0062] R.sup.12 to R.sup.27 may be separately present or two adjacent ones of R.sup.12 to R.sup.27 may be linked to each other to form a ring.

[0063] In an implementation, L.sup.2 and L.sup.3 in Chemical Formulas 1A to 1C may each independently be, e.g., a single bond or a substituted or unsubstituted phenyl group, e.g., each may be a single bond or a substituted or unsubstituted o-phenyl group, or, e.g., each may be a single bond.

[0064] In an implementation, at least one of R.sup.12 to R.sup.27 in Chemical Formula 1A may be, e.g., deuterium, a substituted or unsubstituted C6 to C30 aryl group, a cyano group, or a halogen. In an implementation, at least one of R.sup.12 to R.sup.24 in Chemical Formula 1B may be, e.g., deuterium, a substituted or unsubstituted C6 to C30 aryl group, a cyano group, or a halogen. In an implementation, at least one of R.sup.12 to R.sup.16 and R.sup.20 to R.sup.24 in Chemical Formula 1C may independently be, e.g., deuterium, a substituted or unsubstituted C6 to C30 aryl group, a cyano group, or a halogen.

[0065] In an implementation, at least one of R.sup.12 to R.sup.27 in Chemical Formula 1A, at least one of R.sup.12 to R.sup.24 in Chemical Formula 1B, and at least one of R.sup.12 to R.sup.16 and R.sup.20 to R.sup.24 in Chemical Formula 1C may be, e.g., a substituted or unsubstituted C6 to C30 aryl group, e.g., a substituted or unsubstituted phenyl group, a substituted or unsubstituted biphenyl group, a substituted or unsubstituted terphenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted anthracenyl group, a substituted or unsubstituted phenanthrenyl group, or a substituted or unsubstituted triphenylene group.

[0066] In an implementation, at least one of each substituent in Chemical Formula 1 and Chemical

Formulas 1A to 1C may be substituted with deuterium. The number of substituted deuterium atoms may be 1 to the maximum number of hydrogens in the chemical formula, e.g., 1 to 40 or 1 to 30. [0067] In an implementation, the second compound may be represented by one of Chemical Formula 2a to Chemical Formula 2d.

##STR00009## ##STR00010##

[0068] In Chemical Formulae 2a to 2d, L.sup.8, Ar.sup.7, R.sup.30 to R.sup.33, R.sup.34', R.sup.34'', R.sup.34''', and R.sup.35 to R.sup.42 may be defined the same as those of Chemical Formula 2.

[0069] In an implementation, L.sup.8 of Chemical Formula 2, Chemical Formula 2a to Chemical Formula 2d may be, e.g., a single bond, a substituted or unsubstituted phenylene group, a substituted or unsubstituted biphenylene group, or a substituted or unsubstituted terphenylene group.

[0070] In an implementation, Ar.sup.7 of Chemical Formula 2, and Chemical Formula 2a to Chemical Formula 2d may be, e.g., a substituted or unsubstituted phenyl group, a substituted or unsubstituted biphenyl group, a substituted or unsubstituted terphenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted anthracenyl group, a substituted or unsubstituted triphenylene group, a substituted or unsubstituted carbazolyl group, a substituted or unsubstituted benzothiophenyl group, a substituted or unsubstituted dibenzothiophenyl group, a substituted or unsubstituted benzofuranyl group, a substituted or unsubstituted dibenzofuranyl group, a substituted or unsubstituted benzosilolyl group, a substituted or unsubstituted dibenzosilolyl group, a substituted or unsubstituted fluorenyl group, or a substituted or unsubstituted silyl group.

[0071] In an implementation, R.sup.30 to R.sup.33, R.sup.34', R.sup.34'', R.sup.34''', and R.sup.35 to R.sup.42 of Chemical Formula 2 and Chemical Formula 2a to Chemical Formula 2d may each independently be, e.g., hydrogen, deuterium, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted biphenyl group, a substituted or unsubstituted carbazolyl group, a substituted or unsubstituted benzothiophenyl group, a substituted or unsubstituted dibenzothiophenyl group, a substituted or unsubstituted benzofuranyl group, a substituted or unsubstituted dibenzofuranyl group, a substituted or unsubstituted benzosilolyl group, a substituted or unsubstituted dibenzosilolyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted silyl group, or a cyano group.

[0072] In an implementation, at least one of Ar.sup.7, R.sup.30 to R.sup.33, R.sup.34', R.sup.34'', R.sup.34''', and R.sup.35 to R.sup.42 in Chemical Formula 2 and Chemical Formula 2a to Chemical Formula 2d may be, e.g., a substituted or unsubstituted carbazolyl group.

[0073] In an implementation, at least one of each substituent in Chemical Formula 2 and Chemical Formula 2a to Chemical Formula 2d may be substituted with deuterium. The number of substituted deuterium atoms may be 1 to the maximum number of hydrogens in the chemical formula, e.g., 1 to 40 or 1 to 30.

[0074] As an example, the first compound may be a compound of Group 1.

##STR00011## ##STR00012## ##STR00013## ##STR00014## ##STR00015## ##STR00016##
##STR00017## ##STR00018## ##STR00019## ##STR00020## ##STR00021## ##STR00022##
##STR00023## ##STR00024## ##STR00025## ##STR00026## ##STR00027## ##STR00028##
##STR00029## ##STR00030## ##STR00031## ##STR00032## ##STR00033## ##STR00034##
##STR00035## ##STR00036## ##STR00037## ##STR00038## ##STR00039## ##STR00040##

[0075] (Dn indicates the number of hydrogen atoms replaced by deuterium, and indicates a structure in which one or more deuterium atoms are substituted.)

[0076] In an implementation, the second compound may be a compound of Group 2.

##STR00041## ##STR00042## ##STR00043## ##STR00044## ##STR00045## ##STR00046##
##STR00047## ##STR00048## ##STR00049## ##STR00050## ##STR00051## ##STR00052##

##STR00053## ##STR00054## ##STR00055## ##STR00056## ##STR00057## ##STR00058##
##STR00059## ##STR00060## ##STR00061## ##STR00062## ##STR00063## ##STR00064##
##STR00065## ##STR00066## ##STR00067## ##STR00068## ##STR00069## ##STR00070##
##STR00071## ##STR00072## ##STR00073## ##STR00074## ##STR00075## ##STR00076##
##STR00077## ##STR00078## ##STR00079## ##STR00080##
##STR00081##

[0077] (Dn indicates the number of hydrogen atoms replaced by deuterium, and indicates a structure in which one or more deuterium atoms are substituted.)

[0078] The composition for an organic optoelectronic device may include the first compound and the second compound (e.g., mixed) in various ratios.

[0079] In an implementation, the composition for an organic optoelectronic device may include the first compound and the second compound in a weight ratio of about 10:90 to about 90:10, e.g., about 20:80 to about 80:20, about 30:70 to about 70:30, about 40:60 to about 60:40, or about 50:50.

[0080] In an implementation, the first compound may be included in an amount equal to or greater than the second compound. In an implementation, the first compound may be included in about 50 wt % to about 90 wt %, based on a total weight of the first compound and the second compound.

[0081] In an implementation, the first compound may be included in less or the same amount as the second compound. In an implementation, the first compound may be included in about 10 wt % to about 50 wt %, based on a total weight of the first compound and the second compound.

[0082] The composition for an organic optoelectronic device may further include a light-emitting dopant in addition to the first compound and the second compound.

[0083] The light-emitting dopant is a material mixed with the composition for an organic optoelectronic device in a small amount to cause light emission, and may be a material such as a metal complex that emits light by multiple excitation into a triplet or more. The light-emitting dopant may be, e.g., an inorganic, organic, or organic/inorganic compound, and may be included in one or two or more types.

[0084] The light-emitting dopant may be, e.g., a phosphorescent sensitizer, a fluorescent dopant, or a combination thereof.

[0085] The phosphorescent sensitizer may be an organometallic compound and may effectively transfer energy received from the host to the fluorescent dopant. The phosphorescent sensitizer may increase energy transfer to the fluorescent dopant, causing excitons formed in the light emitting layer to emit light quickly inside the light emitting layer, thereby reducing deterioration of the light emitting diode.

[0086] The phosphorescent sensitizer may be, e.g., an organo-metal compound including iridium (Ir), platinum (Pt), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), thulium (Tm), rhodium (Rh), or a combination thereof, and may be, e.g., an organo-metal compound including an organic ligand including a nitrogen-containing ring. The nitrogen-containing ring may be, e.g., a substituted or unsubstituted pyridine, a substituted or unsubstituted pyrimidine, a substituted or unsubstituted triazine, a substituted or unsubstituted carbazole, a substituted or unsubstituted imidazole, a substituted or unsubstituted benzoimidazole, or a combination thereof.

[0087] In an implementation, the phosphorescent sensitizer may be, e.g., one of Compounds P1 to P52:

##STR00082## ##STR00083## ##STR00084## ##STR00085## ##STR00086## ##STR00087##
##STR00088## ##STR00089## ##STR00090## ##STR00091## ##STR00092##

[0088] The fluorescent dopant may be, e.g., a polycyclic compound, and may help improve the luminous efficiency and life-span characteristics of the light emitting diode by receiving energy transfer within the light emitting layer due to high absorbance.

[0089] The fluorescent dopant may be, e.g., a condensed polycyclic compound including bromine (B), nitrogen (N), or a combination thereof. In an implementation, the fluorescent dopant may

include, e.g., one of Compounds D1 to D30.

##STR00093## ##STR00094## ##STR00095## ##STR00096## ##STR00097## ##STR00098##
##STR00099## ##STR00100## ##STR00101##

[0090] The phosphorescent sensitizer and the fluorescent dopant may each be included in an amount of less than or equal to about 20 wt %, and within the above range, about 0.1 wt % to about 20 wt %, about 0.1 wt % to about 15 wt %, about 0.1 wt % to about 10 wt %, about 0.1 wt % to about 7 wt %, about 0.1 wt % to about 5 wt %, about 0.1 wt % to about 4 wt %, about 1 wt % to about 20 wt %, about 1 wt % to about 15 wt %, about 1 wt % to about 10 wt %, about 1 wt % to about 7 wt %, about 1 wt % to about 5 wt %, or about 1 wt % to about 4 wt %, based on a total weight of the composition for an organic optoelectronic device.

[0091] The composition for an organic optoelectronic device may further include an additive, and the additive may include, e.g., an organic material, an inorganic material, an organic/inorganic material, or a combination thereof.

[0092] Hereinafter, an organic optoelectronic device using the aforementioned composition for an organic optoelectronic device will be described.

[0093] The organic optoelectronic device may be, e.g., an organic light emitting diode, an organic photoelectric device, or an organic solar cell. In an implementation, an organic optoelectronic device may be an organic light emitting diode.

[0094] The organic optoelectronic device may include an anode and a cathode facing each other, and an organic layer between the anode and the cathode, and the organic layer may include the aforementioned composition. The organic layer may include an active layer such as a light emitting layer or a light absorbing layer, and the aforementioned composition may be included in the active layer. The organic layer may include an auxiliary layer between the anode and the active layer and/or between the cathode and the active layer, and the aforementioned composition may be included in the auxiliary layer.

[0095] FIG. 1 is a cross-sectional view showing an example of an organic light emitting diode, which is an example of an organic optoelectronic device according to some embodiments.

[0096] Referring to FIG. 1, the organic light emitting diode **100** according to some embodiments includes an anode **110** and a cathode **120** facing each other, and a light emitting layer **130** between the anode **110** and the cathode **120**.

[0097] The anode **110** may be made of a conductor with a high work function to facilitate hole injection, e.g., and may be made of a metal, a metal oxide, and/or a conductive polymer. The anode **110** may be made of a metal such as nickel, platinum, vanadium, chromium, copper, zinc, gold, or an alloy thereof, a metal oxide such as zinc oxide, indium oxide, indium tin oxide (ITO), and indium zinc oxide (IZO); a combination of a metal and an oxide such as ZnO and Al or SnO₂ and Sb; or a conductive polymer such as poly(3-methylthiophene), poly(3,4-(ethylene-1,2-dioxy)thiophene) (PEDOT), polypyrrole, or polyaniline.

[0098] The cathode **120** may be made of a conductor with a low work function to facilitate electron injection, e.g., and may be made of a metal, a metal oxide, and/or a conductive polymer. The cathode **120** may be made of a metal such as magnesium, calcium, sodium, potassium, titanium, indium, yttrium, lithium, gadolinium, aluminum, silver, tin, lead, cesium, barium, or an alloy thereof, or a multilayer structure material such as LiF/Al, LiO₂/Al, LiF/Ca, and BaF₂/Ca.

[0099] The light emitting layer **130** may include the aforementioned composition for organic optoelectronic devices as a mixed host. The light emitting layer **130** may further include another organic compound as a mixed host. The light emitting layer **130** may further include the aforementioned light-emitting dopant and may include a fluorescent dopant, a phosphorescent sensitizer, or a combination thereof as described above. As an example, the light emitting layer **130** may emit light in a blue light-emitting spectrum by combining the aforementioned composition for an organic optoelectronic device and a light-emitting dopant. At least one of the aforementioned first and second compounds of the composition for an organic optoelectronic device has a high

triplet energy level of greater than or equal to about 2.8 eV, so that exciton transfer to the blue light-emitting dopant may be easy, and thus an organic optoelectronic device having high-efficiency and long life-span may be realized. The peak wavelength of the blue emission spectrum may fall within, e.g., about 410 nm to about 480 nm, and within this range may fall within about 420 nm to about 470 nm or about 430 nm to about 470 nm.

[0100] In an implementation, the aforementioned composition for an organic optoelectronic device may include a first compound, which is a bipolar compound with relatively strong electron transport characteristics, and a second compound, which is a compound with relatively strong hole transport characteristics, so that luminous efficiency may be increased by increasing a balance of electrons and holes within the light emitting layer **130**, and at the same time life-span may be improved by reducing the non-combined charges due to the imbalance in the mobility of electrons and holes, compared to the case where the first compound alone or the second compound alone is used.

[0101] In an implementation, in the organic light emitting diode **100** including the light emitting layer **130** using the composition for organic optoelectronic devices as a mixed host, the holes and electrons injected from the anode **110** and the cathode **120** may appropriately be distributed within the light emitting layer **130**, the mobility may be finely controlled to an appropriate level, and exciton generation within the light emitting layer **130** may be strongly induced, thereby increasing the light emitting efficiency of the light emitting layer **130**.

[0102] In addition, due to a difference in mobility within the light emitting layer **130** of holes and electrons injected from the anode **110** and the cathode **120**, respectively, generation of exciton at inappropriate locations, such as the interface between the light emitting layer **130** and adjacent layers, and/or accumulation of non-combined charges at the interface between the light emitting layer **130** and adjacent layers may be reduced or prevented.

[0103] Accordingly, it is possible to reduce or prevent the roll-off phenomenon in which the luminous efficiency of the organic light emitting diode **100** rapidly decreases due to non-luminescent excitons and/or non-combined charges, thus ultimately improving life-span of the organic light emitting diode **100**.

[0104] The organic light emitting diode **100** may be manufactured by forming an anode **110** or a cathode **120** on a substrate, forming a light emitting layer using dry film forming methods such as vacuum evaporation, sputtering, plasma plating, and ion plating, and forming a cathode **120** or an anode **110** thereon.

[0105] FIG. 2 is a cross-sectional view showing another example of an organic light emitting diode, which is an example of an organic optoelectronic device according to some embodiments.

[0106] Referring to FIG. 2, the organic light emitting diode **100** according to the present embodiments includes an anode **110**, a cathode **120**, and a light emitting layer **130**, similar to the aforementioned embodiments. The organic light emitting diode **100** according to the present embodiments may further include a hole transport layer **140**, a hole transport auxiliary layer **150**, and an electron transport layer **160**.

[0107] The hole transport layer **140** may be located between the anode **110** and the light emitting layer **130**, and the hole transport auxiliary layer **150** may be located between the light emitting layer **130** and the hole transport layer **140**. The electron transport layer **160** may be located between the cathode **120** and the light emitting layer **130**.

[0108] The hole transport layer **140** may facilitate hole transfer from the anode **110** to the light emitting layer **130**, and may include, e.g., an amine compound. In an implementation, the amine compound may have at least one aryl group and/or heteroaryl group with hole characteristics. In an implementation, the amine compound may be represented by Chemical Formula 6a or Chemical Formula 6b.

##STR00102##

[0109] In Chemical Formula 6a or Chemical Formula 6b, Ar.sup.a to Ar.sup.g may each

independently be, e.g., hydrogen, deuterium, a substituted or unsubstituted C1 to C20 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, or a combination thereof.

[0110] In an implementation, at least one of Ar.sup.a to Ar.sup.c and at least one of Ar.sup.d to Ar.sup.g may be a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, or a combination thereof

[0111] Ar.sup.h may be, e.g., a single bond, a substituted or unsubstituted C1 to C20 alkylene group, a substituted or unsubstituted C6 to C30 arylene group, a substituted or unsubstituted C2 to C30 heteroarylene group, or a combination thereof.

[0112] The hole transport auxiliary layer **150** may form an interface with the light emitting layer **130** by being located between the hole transport layer **140** and the light emitting layer **130** and in contact with the light emitting layer **130**. The hole transport auxiliary layer **150** may help further reduce or prevent the generation of exciton at inappropriate locations such as the interface between the aforementioned light emitting layer **130** and adjacent layers and/or the accumulation of non-combined charges at the interface between the light emitting layer **130** and adjacent layers. Accordingly, it is possible to further reduce or prevent the roll-off phenomenon in which the luminous efficiency of the organic light emitting diode **100** rapidly decreases due to non-luminescent excitons and/or unbound charges, and thus ultimately improves the life-span of the organic light emitting diode **100**.

[0113] The electron transport layer **160** may further increase electron injection and/or electron mobility and block holes between the cathode **120** and the light emitting layer **130**.

[0114] The electron transport layer **160** may include, e.g., a compound of Group 5.

##STR00103## ##STR00104## ##STR00105## ##STR00106## ##STR00107## ##STR00108##

[0115] The organic optoelectronic device, including the aforementioned organic light emitting diodes, may be applied to display devices.

[0116] The following Examples and Comparative Examples are provided in order to highlight characteristics of one or more embodiments, but it will be understood that the Examples and Comparative Examples are not to be construed as limiting the scope of the embodiments, nor are the Comparative Examples to be construed as being outside the scope of the embodiments. Further, it will be understood that the embodiments are not limited to the particular details described in the Examples and Comparative Examples.

[0117] Hereinafter, starting materials and reactants used in Examples and Synthesis Examples were purchased from Sigma-Aldrich Co. Ltd., TCI Inc., Tokyo chemical industry or P&H tech as far as there is no particular comment or were synthesized by known methods.

Preparation of Compound for Organic Optoelectronic Device

[0118] The compounds were synthesized through the following steps.

(Synthesis of First Compound)

Synthesis Example 1

##STR00109##

First Step: Synthesis of Compound I-a-1-1

[0119] 20.0 g of carbazole, 28.8 g of 1-bromo-3-chloro-2-fluorobenzene, 106 g of potassium phosphate and 850 ml of DMF were mixed, and then stirred at 170° C. for 24 hours. After cooling the mixture to ambient temperature, 1,000 ml of distilled water was added, and the resulting solid product was filtered and column-purified to synthesize Compound I-A-1-1.

Second Step: Synthesis of Compound I-a-1-2

[0120] 45 g of Compound I-A-1-1, 38 g of bis(pinacolato)diboron, 5.2 g of 1,1'-bis(diphenylphosphino)ferrocene]dichloropalladium(II), 37 g of potassium acetate, and 600 ml of toluene were mixed and stirred at 120° C. for 12 hours. The mixture was then concentrated, and column purified to synthesize Compound I-A-1-2.

Third Step: Synthesis of Compound I-a-1-3

[0121] 32 g of Compound I-A-1-2, 42 g of 9,9'-(6-chloro-1,3,5-triazine-2,4-diyl)bis(9H-carbazole), 4.6 g of tetrakis(triphenylphosphine)palladium(0), 33 g of potassium carbonate, 260 ml of tetrahydrofuran, and 130 ml of distilled water were mixed and stirred at 80° C. for 18 hours. 200 ml of methanol and 300 ml of distilled water were added to the mixture cooled to ambient temperature, and the solid product was filtered and column-purified to synthesize Compound I-A-1-3.

Fourth Step: Synthesis of Compound a-1

[0122] 40 g of Compound I-A-1-3, 0.7 g of palladium(II) acetate, 3.4 g of tricyclohexylphosphine tetrafluoroborate, 16 g of potassium carbonate, and 300 ml of dimethylformamide were mixed and stirred at 140° C. for 20 hours. 500 ml of distilled water was added to the mixture cooled to ambient temperature, the solid product was filtered, and then column-purified to synthesize Compound A-1.

(Synthesis of Second Compound)

Synthesis Example 2: Synthesis of Compound E-72

##STR00110##

[0123] Compound E-72 was synthesized by referring to the method disclosed in Korean Patent Publication No. 10-2023-0155972.

Comparative Synthesis Example 1: Synthesis of Compound HT-1

##STR00111##

[0124] Comparative Compound HT-1 was synthesized by referring to the method described in Korean Patent Publication No. 10-2023-0037447.

[0125] Manufacture of Organic Light Emitting Diode

Example 1

[0126] A glass substrate coated with a thin film of ITO (indium tin oxide) was ultrasonically cleaned with distilled water. After washing with the distilled water, the glass substrate was ultrasonically washed with isopropyl alcohol, acetone, or methanol, and dried and then, moved to a plasma cleaner, cleaned by using oxygen plasma for 10 minutes, and moved to a vacuum depositor. The prepared ITO transparent electrode was used as an anode, Compound A doped with 3% NDP-9 (Novaled GmbH) was vacuum-deposited on the ITO substrate to form a 100 Å-thick hole injection layer, and Compound A was deposited on the hole injection layer to a thickness of 600 Å to form a hole transport layer. mCP (1,3-bis(carbazol-9-yl)benzene) was deposited to a thickness of 100 Å on the hole transport layer to form a hole transport auxiliary layer. On the hole transport auxiliary layer, Compound A-1 obtained in Synthesis Example 1 and Compound E-72 obtained in Synthesis Example 2 were used simultaneously as hosts, P31 was doped at 13 wt % as a phosphorescent sensitizer, and D3 was doped at 1.5 wt % as a fluorescent dopant to form a 400 Å-thick light emitting layer by vacuum deposition. Herein, Compound A-1 and Compound E-72 were used in a weight ratio of 4:6. Subsequently, BCP (2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline) was deposited on the light emitting layer to a thickness of 50 Å to form an electron transport auxiliary layer, and Compound B and LiQ were simultaneously vacuum deposited in a weight ratio of 1:1 to form a 300 Å-thick electron transport layer. An organic light emitting diode was manufactured by sequentially vacuum depositing 10 Å of LiQ and 1,200 Å of Al on the electron transport layer to form a cathode.

[0127] ITO/Compound A (3% NDP-9 doping, 100 Å)/Compound A (600 Å)/mCP (100 Å)/EML [Host (Compound A-1: Compound E-72): P31: D3=85.5 wt %: 13 wt %: 1.5 wt %] (400 Å)/BCP (50 Å)/Compound B: LiQ (300 Å)/LiQ (10 Å)/Al (1,200 Å).

[0128] Compound A: N-(9,9-diphenyl-9H-fluoren-2-yl)-N,9-diphenyl-9H-carbazol-2-amine

[0129] Compound B: 8-{4-[bis(naphthalene-2-yl)-1,3,5-triazin-2-yl]phenyl}quinoline

##STR00112##

Comparative Example 1

[0130] An organic light emitting diode was manufactured in the same manner as in Example 1

except that Compound A-1 obtained in Synthesis Example 1 was used alone to form the light emitting layer, instead of using Compound A-1 obtained in Synthesis Example 1 and Compound E-72 obtained in Synthesis Example 2 together as the host of the light emitting layer.

Comparative Example 2

[0131] An organic light emitting diode was manufactured in the same manner as in Example 1 except that Compound E-72 obtained in Synthesis Example 2 was used alone to form the light emitting layer, instead of using Compound A-1 obtained in Synthesis Example 1 and Compound E-72 obtained in Synthesis Example 2 together as the host of the light emitting layer.

Comparative Example 3

[0132] An organic light emitting diode was manufactured in the same manner as in Example 1 except that Compound A-1 obtained in Synthesis Example 1 and Compound HT-1 obtained in Comparative Synthesis Example 1 were used to form the light emitting layer, instead of using Compound A-1 obtained in Synthesis Example 1 and Compound E-72 obtained in Synthesis Example 2 together as the host of the light emitting layer.

Evaluation

[0133] The luminous efficiency characteristics of the organic light emitting diodes according to the Example and Comparative Examples were evaluated.

[0134] The specific measurement method is as follows, and the results are in Table 1.

(1) Measurement of Current Density Change Depending on Voltage Change

[0135] The obtained organic light emitting diodes were measured regarding a current value flowing in the unit diode, while increasing the voltage from 0 V to 10 V using a current-voltage meter (Keithley 2400), and the measured current value was divided by area to provide the results.

(2) Measurement of Luminance Change Depending on Voltage Change

[0136] Luminance was measured by using a luminance meter (Minolta Cs-1000A), while the voltage of the organic light emitting diodes was increased from 0 V to 10 V.

(3) Measurement of Luminous Efficiency

[0137] Using the luminance and current density measured from (1) and (2) above and a voltage, the current efficiency (cd/A) at the same current density (10 mA/cm²) was calculated. The luminous efficiency values of the organic light emitting diodes according to the Example and Comparative Examples were calculated as relative values based on Comparative Example 3 and are listed in Table 1.

TABLE-US-00001 TABLE 1 Luminous Host efficiency No. First compound Second compound (%) Example 1 A-1 E-72 120 Comparative A-1 — 103 Example 1 Comparative — E-72 65 Example 2 Comparative A-1 HT-1 100 Example 3

[0138] Referring to Table 1, the organic light emitting diode according to the Example exhibited improved luminous efficiency compared to the organic light emitting diodes according to the Comparative Examples.

[0139] One or more embodiments may provide a composition for an organic optoelectronic device that may achieve high efficiency and long life-span characteristics.

[0140] One or more embodiments may provide an organic optoelectronic device including the composition for an organic optoelectronic device.

[0141] An organic optoelectronic device having high efficiency and a long life-span may be realized.

[0142] Example embodiments have been disclosed herein, and although specific terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purpose of limitation. In some instances, as would be apparent to one of ordinary skill in the art as of the filing of the present application, features, characteristics, and/or elements described in connection with a particular embodiment may be used singly or in combination with features, characteristics, and/or elements described in connection with other embodiments unless otherwise specifically indicated. Accordingly, it will be understood by those of skill in the art that various

changes in form and details may be made without departing from the spirit and scope of the present invention as set forth in the following claims.

Claims

1. A composition for an organic optoelectronic device, the composition comprising: a first compound represented by Chemical Formula 1; and a second compound represented by Chemical Formula 2: ##STR00113## wherein, in Chemical Formula 1, Z^{sup.1} to Z^{sup.3} are each independently N or CR^{sup.a}, wherein R^{sup.a} is hydrogen, deuterium, a substituted or unsubstituted C1 to C20 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, a cyano group, or a halogen, provided that at least two of Z^{sup.1} to Z^{sup.3} are N, L^{sup.1} to L^{sup.3} are each independently a single bond, a substituted or unsubstituted C6 to C20 arylene group, or a substituted or unsubstituted divalent C2 to C20 heterocyclic group, and Ar^{sup.1} to Ar^{sup.3} are each independently a substituted or unsubstituted C6 to C30 aryl group or a substituted or unsubstituted C2 to C30 heterocyclic group, provided that at least one of Ar^{sup.1} to Ar^{sup.3} is a group represented by Chemical Formula A, ##STR00114## wherein, in Chemical Formula A, R^{sup.1} to R^{sup.11} are each independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, a substituted or unsubstituted amine group, a substituted or unsubstituted silyl group, a cyano group, a halogen or a linking point with Chemical Formula 1, and R^{sup.1} to R^{sup.11} are separately present or two adjacent ones of R^{sup.1} to R^{sup.11} are linked to each other to form a ring, ##STR00115## wherein, in Chemical Formula 2, L^{sup.7} and L^{sup.8} are each independently a single bond or a substituted or unsubstituted C6 to C30 arylene group, Ar^{sup.7} is a substituted or unsubstituted C6 to C30 aryl group or a substituted or unsubstituted C2 to C30 heterocyclic group, and R^{sup.30} to R^{sup.33}, R^{sup.34'}, R^{sup.34''}, R^{sup.34'''}, and R^{sup.35} to R^{sup.42} are each independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, a substituted or unsubstituted amine group, a substituted or unsubstituted silyl group, a cyano group, or a halogen.
2. The composition for an organic optoelectronic device as claimed in claim 1, wherein at least one of Ar^{sup.1} to Ar^{sup.3} is a substituted or unsubstituted C6 to C30 aryl group or a substituted or unsubstituted carbazolyl group.
3. The composition for an organic optoelectronic device as claimed in claim 2, wherein: one of Ar^{sup.1} to Ar^{sup.3} is the group represented by Chemical Formula A, and the remaining two of Ar^{sup.1} to Ar^{sup.3} are each independently a substituted or unsubstituted C6 to C30 aryl group or a substituted or unsubstituted carbazolyl group.
4. The composition for an organic optoelectronic device as claimed in claim 2, wherein: one of Ar^{sup.1} to Ar^{sup.3} is a substituted or unsubstituted C6 to C30 aryl group or a substituted or unsubstituted carbazolyl group, and the remaining two of Ar^{sup.1} to Ar^{sup.3} are the group represented by Chemical Formula A.
5. The composition for an organic optoelectronic device as claimed in claim 1, wherein the first compound is represented by one of Chemical Formulae 1A to 1C: ##STR00116## wherein, in Chemical Formulae 1A to 1C, Z^{sup.1} to Z^{sup.3} and L^{sup.1} to L^{sup.3} are defined the same as those of Chemical Formula 1, Ar^{sup.1} is the group represented by Chemical Formula A, R^{sup.12} to R^{sup.27} are each independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, a substituted or unsubstituted amine group, a substituted or unsubstituted silyl group, a cyano group, or a halogen, and R^{sup.12} to R^{sup.27} are separately present or two adjacent ones of R^{sup.12} to R^{sup.27} are linked to each other to form a ring.

6. The composition for an organic optoelectronic device as claimed in claim 1, wherein Chemical Formula 2 is represented by one of Chemical Formulae 2a to 2d: ##STR00117## wherein, in Chemical Formulae 2a to 2d, L.sup.8, Ar.sup.7, R.sup.30 to R.sup.33, R.sup.34', R.sup.34'', R.sup.34''', and R.sup.35 to R.sup.42 are defined the same as those of Chemical Formula 2.
7. The composition for an organic optoelectronic device as claimed in claim 6, wherein: L.sup.8 is a single bond, a substituted or unsubstituted phenylene group, a substituted or unsubstituted biphenylene group, or a substituted or unsubstituted terphenylene group, and Ar.sup.7 is a substituted or unsubstituted phenyl group, a substituted or unsubstituted biphenyl group, a substituted or unsubstituted terphenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted anthracenyl group, a substituted or unsubstituted triphenylene group, a substituted or unsubstituted carbazolyl group, a substituted or unsubstituted benzothiophenyl group, a substituted or unsubstituted dibenzothiophenyl group, a substituted or unsubstituted benzofuranyl group, a substituted or unsubstituted dibenzofuranyl group, a substituted or unsubstituted benzosilolyl group, a substituted or unsubstituted dibenzosilolyl group, a substituted or unsubstituted fluorenyl group, or a substituted or unsubstituted silyl group.
8. The composition for an organic optoelectronic device as claimed in claim 6, wherein at least one of Ar.sup.7, R.sup.30 to R.sup.33, R.sup.34', R.sup.34'', R.sup.34''', and R.sup.35 to R.sup.42 is a substituted or unsubstituted carbazolyl group.
9. The composition for an organic optoelectronic device as claimed in claim 1, wherein the first compound and the second compound are included in a weight ratio of about 10:90 to about 90:10.
10. An organic optoelectronic device, comprising: an anode and a cathode facing each other, and a light emitting layer between the anode and the cathode, wherein the light emitting layer includes the composition for an organic optoelectronic device as claimed in claim 1.
11. The organic optoelectronic device as claimed in claim 10, wherein the light emitting layer further includes a fluorescent dopant, a phosphorescent sensitizer, or a combination thereof.
12. The organic optoelectronic device as claimed in claim 11, wherein: the fluorescent dopant is a condensed polycyclic compound including bromine (B), nitrogen (N), or a combination thereof, and the phosphorescent sensitizer is an organometallic compound.
13. The organic optoelectronic device as claimed in claim 10, wherein the light emitting layer emits light in a blue emission spectrum.
14. The organic optoelectronic device as claimed in claim 10, further comprising: a hole transport layer between the anode and the light emitting layer, and a hole transport auxiliary layer between the light emitting layer and the hole transport layer.
15. A display device comprising the organic optoelectronic device as claimed in claim 10.
-