

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250286412

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

MURAKAWA; Tesshu et al.

ROTARY ELECTRIC MACHINE, NON-ORIENTED ELECTRICAL STEEL SHEET, LAMINATED CORE, METHOD FOR MANUFACTURING ROTARY ELECTRIC MACHINE, AND METHOD FOR MANUFACTURING LAMINATED CORE

Abstract

This rotary electric machine includes a stator, a rotor, and a housing that houses the stator and the rotor, A which is an $\{111\} \langle 211 \rangle$ orientation strength of a base steel sheet of a non-oriented electrical steel sheet included in the stator is less than 15, B which is an $\{111\} \langle 211 \rangle$ orientation strength of a base steel sheet of the non-oriented electrical steel sheet included in the rotor is 2 to 30, the A and the B satisfy a relationship of $B/A > 1.0$, C which is an $\{411\} \langle 011 \rangle$ orientation strength of a base steel sheet of the non-oriented electrical steel sheet included in the stator is 2 to 50, D which is an $\{411\} \langle 011 \rangle$ orientation strength of a base steel sheet of the non-oriented electrical steel sheet included in the rotor is 1 to 40, and the C and D satisfy a relationship of $C/D > 1.0$.

Inventors: MURAKAWA; Tesshu (Tokyo, JP), KANO; Satoshi (Tokyo, JP)

Applicant: NIPPON STEEL CORPORATION (Tokyo, JP)

Family ID: 86397055

Assignee: NIPPON STEEL CORPORATION (Tokyo, JP)

Appl. No.: 18/700758

Filed (or PCT Filed): November 18, 2022

PCT No.: PCT/JP2022/042866

Foreign Application Priority Data

JP 2021-187952

Nov. 18, 2021

Publication Classification

Int. Cl.: **H02K1/02** (20060101); **B32B15/01** (20060101); **C21D6/00** (20060101); **C21D8/12** (20060101); **C21D9/46** (20060101); **C22C38/00** (20060101); **C22C38/02** (20060101); **C22C38/04** (20060101); **C22C38/06** (20060101); **C22C38/12** (20060101); **C22C38/14** (20060101); **C22C38/20** (20060101); **C22C38/30** (20060101); **C22C38/34** (20060101); **C22C38/38** (20060101); **C22C38/58** (20060101); **C22C38/60** (20060101); **H01F1/147** (20060101)

U.S. Cl.:

CPC **H02K1/02** (20130101); **C21D6/002** (20130101); **C21D6/004** (20130101); **C21D6/005** (20130101); **C21D6/008** (20130101); **C21D8/1222** (20130101); **C21D8/1233** (20130101); **C21D8/1261** (20130101); **C21D8/1266** (20130101); **C21D9/46** (20130101); **C22C38/001** (20130101); **C22C38/002** (20130101); **C22C38/004** (20130101); **C22C38/008** (20130101); **C22C38/02** (20130101); **C22C38/04** (20130101); **C22C38/06** (20130101); **C22C38/12** (20130101); **C22C38/14** (20130101); **C22C38/20** (20130101); **C22C38/30** (20130101); **C22C38/34** (20130101); **C22C38/38** (20130101); **C22C38/58** (20130101); **C22C38/60** (20130101); **H01F1/14775** (20130101); **B32B15/011** (20130101); **B32B2307/208** (20130101); **B32B2311/30** (20130101); **B32B2457/00** (20130101); **C22C2202/02** (20130101)

Background/Summary

TECHNICAL FIELD OF THE INVENTION

[0001] The present invention relates to a rotary electric machine, a non-oriented electrical steel sheet, a laminated core, a method for manufacturing a rotary electric machine, and a method for manufacturing a laminated core.

[0002] The present application claims priority based on Japanese Patent Application No. 2021-187952 filed in Japan on Nov. 18, 2021, the contents of which are incorporated herein by reference. RELATED ART

[0003] In the present specification, a non-oriented electrical steel sheet before lamination constituting a stator core may be referred to as a core material of a stator, a non-oriented electrical steel sheet before lamination constituting a rotor core may be referred to as a core material of a rotor, and a combination of the stator core and the rotor core may be referred to as a motor core.

[0004] An electrical steel sheet, particularly a non-oriented electrical steel sheet, is used as a core material of a rotary electric machine. For example, a rotary electric machine is used as a drive motor mounted on a hybrid vehicle, a fuel cell vehicle, an electric vehicle, or the like. Both noise reduction and high torque are required for future automobile driving motors. The noise of the motor is mainly generated by non-uniform magnetic attraction force. In addition, when a gap between the stator and the rotor becomes non-uniform due to eccentricity of the rotor or the like, the magnetic attraction force also becomes non-uniform, which causes an increase in motor noise.

[0005] Patent Document 1 proposes a non-oriented electrical steel sheet having small magnetic anisotropy and high magnetic flux density, which is effective for improving efficiency in an actual machine motor and reducing noise during rotation. In the motor, a magnetic flux flows through the air gap between the stator portion and the rotor portion, and this magnetic flux interaction generates torque in the rotor. The stronger the anisotropy of the electrical steel sheet as the stator material, that is, the larger the difference in magnetic characteristics in the in-plane direction, the larger the

difference in torque at the rotational position of the rotor. It is described that the variation in torque during rotation causes rotation unevenness and affects noise.

CITATION LIST

Patent Document

[0006] [Patent Document 1] [0007] Japanese Unexamined Patent Application, First Publication No. 2001-49402

SUMMARY OF INVENTION

Problems to be Solved by the Invention

[0008] An object of the present invention is to provide a rotary electric machine that realizes both noise reduction and high torque required for an automobile driving motor, a non-oriented electrical steel sheet suitable as a material of a rotor and a stator of such a rotary electric machine, a laminated core formed by laminating non-oriented electrical steel sheets suitably used for a stator or a rotor of a rotary electric machine, and a method for manufacturing thereof.

Means for Solving the Problem

[0009] The noise of the motor is mainly generated by non-uniform magnetic attraction force between the stator and the rotor. When the gap between the stator and the rotor becomes non-uniform due to eccentricity of the rotor or the like, the magnetic attraction force also becomes non-uniform, which causes an increase in noise.

[0010] In the $\{111\}$ $\langle uvw \rangle$ orientation of the non-oriented electrical steel sheet, it has been found that anisotropy of Young's modulus in the in-plane direction (proportional coefficient of elongation and stress in elastic deformation region) is small.

[0011] Based on this finding, the present inventors have further conducted studies, and resultantly found that when an electrical steel sheet (non-oriented electrical steel sheet) in which the $\{111\}$ $\langle 211 \rangle$ orientation is enriched is used as a core material of a rotor of a permanent magnet (PM) motor, anisotropy of elongation deformation of the steel sheet of the core material of the rotor with respect to centrifugal force during rotation of the rotor is suppressed, and noise can be reduced. In general, since the $\{111\}$ $\langle 211 \rangle$ orientation is difficult to magnetize, use as a core material of a motor is avoided, but for the core material of the rotor of the PM motor in which magnetization is secured by a permanent magnet, application of the electrical steel sheet in which the $\{111\}$ $\langle 211 \rangle$ orientation is enriched is not a great disadvantage.

[0012] On the other hand, it is disadvantageous to use the electrical steel sheet in which the $\{111\}$ $\langle 211 \rangle$ orientation is enriched as a core material of a stator in which magnetization that generates motor torque is secured by magnetization of the core material. Therefore, the present inventors have found that by using an electrical steel sheet (non-oriented electrical steel sheet) enriched in the $\{411\}$ $\langle 011 \rangle$ orientation having excellent magnetic characteristics for the core material of the stator and using electrical steel sheets enriched in different orientations for the core material of the rotor and the core material of the stator, both noise reduction and high torque can be achieved in a rotary electric machine obtained using these electrical steel sheets as materials.

[0013] Here, $\{lmn\}$ $\langle uvw \rangle$ represents the orientation of a crystal. $\{lmn\}$ refers to the Miller indices in the direction parallel to the normal direction of the rolled surface, and $\langle uvw \rangle$ refers to the Miller indices in the direction parallel to the rolling direction in the electrical steel sheet production step. In addition, since the present invention controls the rotational torque variation caused by the in-plane anisotropy of the characteristics of the electrical steel sheet, the present invention also defines the integrated orientation strength in the rolling direction.

[0014] In order to solve the above problem, the present invention has the following configuration.

[0015] [1] A rotary electric machine according to an aspect of the present invention includes a stator; a rotor; and a housing that houses the stator and the rotor, wherein A which is an $\{111\}$ $\langle 211 \rangle$ orientation strength of a base steel sheet of a non-oriented electrical steel sheet included in the stator is less than 15, B which is an $\{111\}$ $\langle 211 \rangle$ orientation strength of a base steel sheet of a non-oriented electrical steel sheet included in the rotor is 2 to 30, and the A and the B satisfy a

relationship of $B/A > 1.0$, C which is an $\{411\} \langle 011 \rangle$ orientation strength of the base steel sheet of the non-oriented electrical steel sheet included in the stator is 2 to 50, D which is an $\{411\} \langle 011 \rangle$ orientation strength of the base steel sheet of the non-oriented electrical steel sheet included in the rotor is 1 to 40, and the C and the D satisfy a relationship of $C/D > 1.0$, and the base steel sheets of the non-oriented electrical steel sheet included in the rotor and the non-oriented electrical steel sheet included in the stator each having a chemical composition including, in mass %, C: 0.0100% or less, Si: 0.5000 to 4.0000%, sol.Al: 0.0001 to 1.0000%, S: 0.0100% or less, N: 0.0100% or less, one or more selected from the group consisting of Mn, Ni, Co, Pt, Pb, Cu, and Au: 0.1000 to 5.0000% in total, Cr: 0 to 2.0000%, Sn: 0 to 0.4000%, Sb: 0 to 0.4000%, P: 0 to 0.4000%, Ti: 0 to 0.1000%, Nb: 0 to 0.1000%, Zr: 0 to 0.1000%, V: 0 to 0.1000%, and the remainder of Fe and impurities.

[0016] [2] In the rotary electric machine according to the above [1], in which, in the non-oriented electrical steel sheet included in the rotor, the B and E which is an $\{111\} \langle 011 \rangle$ orientation strength may satisfy a relationship of $B/E > 1.0$.

[0017] [3] In the rotary electric machine according to the above [1] or [2], in which, in the non-oriented electrical steel sheet included in the stator, the C and F which is an $\{100\} \langle 011 \rangle$ orientation strength may satisfy a relationship of $C/F > 1.0$.

[0018] [4] In the rotary electric machine according to any one of the above [1] to [3], in which difference in a total of the Si content, the Mn content, and the sol.Al content in the base steel sheets between the non-oriented electrical steel sheet included in the stator and the non-oriented electrical steel sheet included in the rotor may be within 0.20 mass %, and an average grain size of the non-oriented electrical steel sheet included in the stator may be larger than an average grain size of the non-oriented electrical steel sheet included in the rotor.

[0019] [5] In the rotary electric machine according to any one of the above [1] to [4], in which when the Si content, the Ti content, and the Nb content in mass % of the base steel sheet of the non-oriented electrical steel sheet included in the stator are respectively denoted by Si.sub.s, Ti.sub.s, and Nb.sub.s, and the Si content, the Ti content, and the Nb content of the base steel sheet of the non-oriented electrical steel sheet included in the rotor are respectively denoted by Si.sub.r, Ti.sub.r, and Nb.sub.r, any one of $Si.sub.s/Si.sub.r > 1.0$, $Ti.sub.r/Ti.sub.s > 1.0$, and $Nb.sub.r/Nb.sub.s > 1.0$ may be satisfied.

[0020] [6] In the rotary electric machine according to any one of the above [1] to [5], in which when the Nb content, the Zr content, the Ti content, the V content, the C content, and the N content in mass % of the base steel sheet of the non-oriented electrical steel sheet included in the stator are respectively denoted by Nb.sub.s, Zr.sub.s, Ti.sub.s, V.sub.s, C.sub.s, and N.sub.s, $0 \leq Nb.sub.s/93 + Zr.sub.s/91 + Ti.sub.s/48 + V.sub.s/51 - (C.sub.s/12 + N.sub.s/14)$ may be satisfied.

[0021] [7] In the rotary electric machine according to any one of the above [1] to [6], in which when the Nb content, the Zr content, the Ti content, the V content, the C content, and the N content of the base steel sheet of the non-oriented electrical steel sheet included in the rotor are respectively denoted by Nb.sub.r, Zr.sub.r, Ti.sub.r, V.sub.r, C.sub.r, and N.sub.r, in mass %, $0 < Nb.sub.r/93 + Zr.sub.r/91 + Ti.sub.r/48 + V/51 - (C.sub.r/12 + N.sub.r/14) < 5.0 \times 10^{-3}$ may be satisfied.

[0022] [8] A non-oriented electrical steel sheet according to another aspect of the present invention includes a base steel sheet; and an insulating coating formed on a surface of the base steel sheet, the base steel sheet having a chemical composition including, in mass %, C: 0.0100% or less, Si: 0.5000 to 4.0000%, sol.Al: 0.0001 to 1.0000%, S: 0.0100% or less, N: 0.0100% or less, one or more selected from the group consisting of Mn, Ni, Co, Pt, Pb, Cu, and Au: 0.1000 to 5.0000% in total, Cr: 0 to 2.0000%, Sn: 0 to 0.4000%, Sb: 0 to 0.4000%, P: 0 to 0.4000%, Ti: 0 to 0.1000%, Nb: 0 to 0.1000%, Zr: 0 to 0.1000%, V: 0 to 0.1000%, and the remainder of Fe and impurities, and in the base steel sheet, an $\{111\} \langle 211 \rangle$ orientation strength being less than 15, and an $\{411\} \langle 011 \rangle$ orientation strength being 2 to 50.

[0023] [9] A non-oriented electrical steel sheet according to another aspect of the present invention includes a base steel sheet; and an insulating coating formed on a surface of the base steel sheet, the base steel sheet having a chemical composition including, in mass %, C: 0.0100% or less, Si: 0.5000 to 4.0000%, sol.Al: 0.0001 to 1.0000%, S: 0.0100% or less, N: 0.0100% or less, one or more selected from the group consisting of Mn, Ni, Co, Pt, Pb, Cu, and Au: 0.1000 to 5.0000% in total, Cr: 0 to 2.0000%, Sn: 0 to 0.4000%, Sb: 0 to 0.4000%, P: 0 to 0.4000%, Ti: 0 to 0.1000%, Nb: 0 to 0.1000%, Zr: 0 to 0.1000%, V: 0 to 0.1000%, and the remainder of Fe and impurities, and in the base steel sheet, an {111} <211> orientation strength being 2 to 30, and an {411} <011> orientation strength being 1 to 40.

[0024] [10] A laminated core according to another aspect of the present invention in which the non-oriented electrical steel sheets according to the above [8] are laminated.

[0025] [11] A laminated core according to another aspect of the present invention in which the non-oriented electrical steel sheets according to the above [9] are laminated.

[0026] [12] In the rotary electric machine according to any one of the above [1] to [7], in which the non-oriented electrical steel sheet included in the stator may be a steel sheet obtained by further performing heat treatment at 600° C. or higher on the non-oriented electrical steel sheet included in the rotor.

[0027] [13] A method for manufacturing a laminated core according to another aspect of the present invention includes a step of processing and laminating the non-oriented electrical steel sheets according to the above [8].

[0028] [14] A method for manufacturing a laminated core according to another aspect of the present invention includes a step of processing and laminating the non-oriented electrical steel sheets according to the above [9].

[0029] [15] A method for manufacturing a rotary electric machine according to another aspect of the present invention includes a step of assembling the laminated core according to the above [10] and the laminated core according to the above [11].

Effects of the Invention

[0030] According to the above aspects of the present invention, it is possible to provide a rotary electric machine that realizes both noise reduction and high torque required for automobile driving motors, a non-oriented electrical steel sheet suitable as a material of a rotor and a stator of such a rotary electric machine, a laminated core formed by laminating non-oriented electrical steel sheets suitably used for a stator or a rotor of a rotary electric machine.

[0031] That is, in the rotary electric machine according to the above aspects of the present invention, by using an electrical steel sheet enriched in the {111} <211> orientation as the rotor core material, the anisotropy of Young's modulus in the in-plane direction is reduced, and the anisotropy of deformation of the rotor core material in the radial direction due to the centrifugal force during the rotor rotation is suppressed, so that the gap between the stator and the rotor is made constant, whereby the motor noise can be suppressed. In addition, by using an electrical steel sheet enriched in the {411} <011> orientation as the core material of the stator, torque of the motor can be increased. Therefore, the rotary electric machine according to the above aspects of the present invention can achieve both noise reduction and high torque.

Description

BRIEF DESCRIPTION OF THE DRAWING

[0032] FIG. 1 is a partial plan view of a motor used in Example.

EMBODIMENT OF THE INVENTION

[0033] Hereinafter, a rotary electric machine according to an embodiment of the present invention (a rotary electric machine according to the present embodiment), a non-oriented electrical steel

sheet according to an embodiment of the present invention (a non-oriented electrical steel sheet according to the present embodiment), a laminated core according to an embodiment (a laminated core according to the present embodiment), and a method for manufacturing the same of the present invention will be described.

[0034] Unless otherwise specified, expression “a to b” concerning numerical values a and b shall mean “a or more and b or less”. In such expression, if a unit is added only to the numerical value b, this unit shall be applied to the numerical value a as well.

[Rotary Electric Machine]

[Non-Oriented Electrical Steel Sheet]

[0035] The rotary electric machine according to the present embodiment has the following constitutions.

[0036] The rotary electric machine according to the present embodiment includes a stator: a rotor; and a housing that houses the stator and the rotor, wherein [0037] A which is an $\{111\} \langle 211 \rangle$ orientation strength of a base steel sheet of a non-oriented electrical steel sheet included in the stator is less than 15, B which is an $\{111\} \langle 211 \rangle$ orientation strength of a base steel sheet of a non-oriented electrical steel sheet included in the rotor is 2 to 30, and the A and the B satisfy a relationship of $B/A > 1.0$, [0038] C which is an $\{411\} \langle 011 \rangle$ orientation strength of the base steel sheet of the non-oriented electrical steel sheet included in the stator is 2 to 50, D which is an $\{411\} \langle 011 \rangle$ orientation strength of the base steel sheet of the non-oriented electrical steel sheet included in the rotor is 1 to 40, and the C and the D satisfy a relationship of $C/D > 1.0$, and [0039] the base steel sheets of the non-oriented electrical steel sheet included in the rotor and the non-oriented electrical steel sheet included in the stator each including [0040] C: 0.0100% or less, Si: 0.5000 to 4.0000%, sol.Al: 0.0001 to 1.0000%, S: 0.0100% or less, N: 0.0100% or less, one or more selected from the group consisting of Mn, Ni, Co, Pt, Pb, Cu, and Au: 0.1000 to 5.0000% in total, in mass %, Cr: 0 to 2.0000%, Sn: 0 to 0.4000%, Sb: 0 to 0.4000%, P: 0 to 0.4000%, Ti: 0 to 0.1000%, Nb: 0 to 0.1000%, Zr: 0 to 0.1000%, V: 0 to 0.1000%, and the remainder having a chemical composition consisting of Fe and impurities.

[0041] Among them, the non-oriented electrical steel sheet included in the rotor (that is a rotor core material) and the non-oriented electrical steel sheet included in the stator (that is a stator core material) are each the non-oriented electrical steel sheet according to the present embodiment.

[0042] The rotary electric machine according to the present embodiment includes at least a stator, a rotor, and a housing that accommodates the stator and the rotor. The stator, the rotor, and the housing are not particularly limited in terms of their shapes and constitutions, and have normal shapes and constitutions.

<Non-Oriented Electrical Steel Sheet>

[0043] The non-oriented electrical steel sheet according to the present embodiment includes a base steel sheet and an insulating coating formed on a surface of the base steel sheet.

[0044] Among them, the non-oriented electrical steel sheet according to the present embodiment is particularly characterized in the chemical composition and texture (orientation strength in each orientation) of the base steel sheet.

[Orientation Strength of Each Orientation of Base Steel Sheet]

[0045] The $\{111\} \langle 211 \rangle$ orientation strength of the base steel sheet of the non-oriented electrical steel sheet mainly represents the integrated strength in the $\{111\}$ orientation in which the anisotropy of Young's modulus in the in-plane direction is relatively small. It is considered that ideally, it is preferable to form a completely random texture when considering reduction of anisotropy in the in-plane direction due to crystal orientation. Alternatively, even if it is not completely random, it is considered preferable to strongly integrate in a specific plane orientation and randomly integrate in an in-plane orientation with respect to the plane orientation, for example, to make the integrated strength for v and w uniform in $\{100\} \langle 0vw \rangle$, and to make the change in the integrated strength in the sheet surface small and random even in the $\{111\}$ orientation.

However, in an electrical steel sheet manufactured through general casting, rolling, and annealing (heat treatment), considerable integration in a specific orientation is inevitable in a base steel sheet, and it is difficult to achieve ideal randomization as described above. In view of such a background, in the non-oriented electrical steel sheet included in the rotor and the stator of the rotary electric machine according to the present embodiment (the non-oriented electrical steel sheet according to the present embodiment), the $\{111\} \langle 211 \rangle$ orientation strength of the base steel sheet is an orientation that should be reliably controlled as intended in a general electrical steel sheet, and is very effective as an index for achieving the suppression of the anisotropy of Young's modulus in the in-plane direction. Furthermore, the $\{111\} \langle 211 \rangle$ orientation strength is an effective index for evaluating magnetic characteristics of the core material of the stator, and in the present embodiment, this orientation is used as one definition for obtaining an effect.

[0046] In addition, the $\{411\} \langle 011 \rangle$ orientation strength of the base steel sheet of the electrical steel sheet indicates that a magnetization easy axis is mainly close to the in-plane direction, and thus the magnetic characteristics are excellent. Here, the magnetization easy axis is a direction in which magnetization is the easiest among the magnetic anisotropy of the crystal, and refers to ridgeline directions ($[100]$, $[010]$, directions) in the crystal having bcc structure. Therefore, in the present embodiment, this orientation is also used as one definition for obtaining an effect.

[0047] In the present specification, the orientation strength of the base steel sheet of the electrical steel sheet may be simply expressed as the orientation strength of the electrical steel sheet (non-oriented electrical steel sheet), but even in this case, the orientation strength means the orientation strength of the base steel sheet.

[0048] In the present specification, the “orientation strength” indicates how many times the diffraction intensity is when the crystal orientation is random. That is, for example, the $\{111\} \langle 211 \rangle$ orientation strength indicates how many times the diffraction intensity of the $\{111\} \langle 211 \rangle$ orientation is higher than that when the crystal orientation is random, when measured by EBSD.

[0049] There are various methods for measuring the crystal orientation strength, but in the measurement of the $\{111\} \langle 211 \rangle$ orientation strength and the $\{411\} \langle 011 \rangle$ orientation strength, first, a rolled surface is polished so that the center of the sheet thickness of the base steel sheets of the non-oriented electrical steel sheet that is the core material of the stator and the core material of the rotor appears, and the polished surface is observed in a region of $960,000 \mu\text{m}^2$ or more by electron back scattering diffraction (EBSD). The observation may be performed in a total area of $960,000 \mu\text{m}^2$ or more, for example, in the range of $800 \mu\text{m} \times 1,200 \mu\text{m}$ or more. In a case where the measurement magnification is not within the range, the measurement may be performed at several sites divided into several small partitions, and for example, 8 or more regions of $200 \mu\text{m} \times 600 \mu\text{m}$ or more may be observed.

[0050] The step interval at the time of measurement is preferably $1 \mu\text{m}$. The upper limit of the step interval is $1/10$ of the average grain size.

[0051] The $\{111\} \langle 211 \rangle$ orientation strength and the $\{411\} \langle 011 \rangle$ orientation strength are obtained from the EBSD observation data.

[0052] A procedure for obtaining the $\{111\} \langle 211 \rangle$ orientation strength and the $\{411\} \langle 011 \rangle$ orientation strength from the EBSD observation data will be described below.

[0053] As described above, the range with an area of $960,000 \mu\text{m}^2$ or more is observed, and at least 100 grains are observed.

[0054] The observation data is analyzed using OIM Analysis software (manufactured by TSL) to create an orientation distribution function (ODF), and the $\{111\} \langle 211 \rangle$ orientation strength and the $\{411\} \langle 011 \rangle$ orientation strength are obtained from the values.

[0055] In the rotary electric machine according to the present embodiment, the $\{111\} \langle 211 \rangle$ orientation strength (A) of the base steel sheet of the non-oriented electrical steel sheet that is the core material of the stator is in the range of less than 15. If the $\{111\} \langle 211 \rangle$ orientation strength (A) exceeds 15, the magnetic characteristics are deteriorated. The range of the $\{111\} \langle 211 \rangle$

orientation strength (A) is preferably 1 to 3.

[0056] In the rotary electric machine according to the present embodiment, the $\{111\} \langle 211 \rangle$ orientation strength (B) of the base steel sheet of the non-oriented electrical steel sheet that is the core material of the rotor is in the range of 2 to 30. When the $\{111\} \langle 211 \rangle$ orientation strength (B) is less than 2, the in-plane anisotropy of Young's modulus increases, and noise during rotation increases. On the other hand, when the $\{111\} \langle 211 \rangle$ orientation strength (B) exceeds 30, the magnetic permeability becomes small, thus the motor efficiency decreases. The range of the orientation strength (B) is preferably 10 to 30.

[0057] In the rotary electric machine according to the present embodiment, in each of the non-oriented electrical steel sheet that is the core material of the stator and the non-oriented electrical steel sheet that is the core material of the rotor, it is necessary that the $\{111\} \langle 211 \rangle$ orientation strength of the base steel sheet has the above range, and at the same time, A and B which are the respective orientation strengths satisfy a relationship of $B/A > 1.0$. When A and B are in the relationship of $B/A > 1.0$, it is possible to achieve both reduction of loss generated in the core of the stator which is easily affected by the magnetic characteristics of the core material and reduction of noise generated in the core of the rotor which is easily affected by the deformation due to the centrifugal force associated with the rotation, and motor characteristics are improved. A and B are in a relationship of preferably $B/A > 1.1$, and more preferably $B/A > 1.2$.

[0058] On the contrary, when A and B are in a relationship of $B/A \leq 1.0$, an electrical steel sheet that is disadvantageous in terms of the deformation with respect to the centrifugal force is applied as the rotor core material, and an electrical steel sheet that is disadvantageous in terms of magnetic characteristics is applied as the stator core material, so that motor loss increases.

[0059] Further, in the rotary electric machine according to the present embodiment, the $\{411\} \langle 011 \rangle$ orientation strength (C) of the base steel sheet of the non-oriented electrical steel sheet that is the core material of the stator is in the range of 2 to 50. When the orientation strength (C) is less than 2, the magnetic characteristics are deteriorated, and the motor characteristics are deteriorated. On the other hand, when the $\{411\} \langle 011 \rangle$ orientation strength (C) exceeds 50, manufacturing becomes difficult. The range of the orientation strength (C) is preferably 5 to 30.

[0060] In the rotary electric machine according to the present embodiment, the $\{411\} \langle 011 \rangle$ orientation strength (D) of the base steel sheet of the non-oriented electrical steel sheet that is the core material of the rotor is 1 to 40. When the $\{411\} \langle 011 \rangle$ orientation strength (D) exceeds 40, the in-plane anisotropy of Young's modulus becomes strong, and noise increases. On the other hand, when the orientation strength (D) is less than 1, heat is easily generated inside the rotor, a permanent magnet is demagnetized, and the characteristics of the motor may be deteriorated. The range of the $\{411\} \langle 011 \rangle$ orientation strength (D) is preferably 3 to 20.

[0061] In the rotary electric machine according to the present embodiment, in each of the core material of the stator and the core material of the rotor (non-oriented electrical steel sheets), it is necessary that the base steel sheet has the $\{411\} \langle 011 \rangle$ orientation strength range described above, and at the same time, C and D which are the respective orientation strengths satisfy a relationship of $C/D > 1.0$. When C and D are in the relationship of $C/D > 1.0$, it is possible to achieve both improvement of the magnetic characteristics of the core of the stator which is easily affected by the magnetic characteristics of the core material and reduction of noise generated in the core of the rotor which is easily affected by the deformation due to the centrifugal force associated with the rotation. C and D are in a relationship of preferably $C/D > 1.1$, and further preferably $C/D > 1.2$.

[0062] On the contrary, when C and D are in a relationship of $C/D \leq 1.0$, an electrical steel sheet that is disadvantageous in terms of the deformation with respect to the centrifugal force is applied as the rotor core material, and an electrical steel sheet that is disadvantageous in terms of magnetic characteristics is applied as the stator core material, so that motor loss increases.

[0063] Here, the orientation strength of the base steel sheets of the core materials (non-oriented electrical steel sheets) of the stator and the rotor will be described. The $\{111\} \langle 211 \rangle$ orientation

strength and the $\{411\} \langle 011 \rangle$ orientation strength defined in the present embodiment roughly have a trade-off relationship. For example, as characteristics, the $\{111\} \langle 211 \rangle$ orientation is an orientation that is not preferable for magnetic characteristics, and the $\{411\} \langle 011 \rangle$ is a preferable orientation for magnetic characteristics. Therefore, in the present embodiment, in the non-oriented electrical steel sheet that is the core material of the stator, control is performed so as to weaken the $\{111\} \langle 211 \rangle$ orientation strength and at the same time to strengthen the $\{411\} \langle 011 \rangle$ orientation strength.

[0064] Also in the metallurgical aspect, in the change in the texture in the steel sheet production step by cold rolling and annealing (recrystallization), for example, according to a change in rolling reduction of cold rolling or a change in annealing temperature, a situation in which an increase in the $\{111\} \langle 211 \rangle$ orientation is accompanied by a decrease in the $\{411\} \langle 011 \rangle$ orientation and a situation in which an increase in the $\{411\} \langle 011 \rangle$ orientation is accompanied by a decrease in the $\{111\} \langle 211 \rangle$ orientation are observed.

[0065] From such a background, in the present embodiment, for example, in the non-oriented electrical steel sheet that is the stator core material, as a result of controlling so as to weaken the $\{111\} \langle 211 \rangle$ orientation strength (A) and increase the $\{411\} \langle 011 \rangle$ orientation strength (C) of the base steel sheet, $A/C < 1.0$ is easily established for the core material of the stator. From the opposite viewpoint, the core material of the stator preferably satisfies $A/C < 1.0$. It is more preferably $A/C < 0.8$, and further preferably $A/C < 0.6$.

[0066] Similarly, in the non-oriented electrical steel sheet that is the core material of the rotor, as a result of controlling so as to strengthen the $\{111\} \langle 211 \rangle$ orientation strength (B) and weaken the $\{411\} \langle 011 \rangle$ orientation strength (D) of the base steel sheet, $B/D > 1.0$ is easily established for the core material of the rotor. From the opposite viewpoint, the core material of the rotor preferably satisfies $B/D > 1.0$. It is more preferably $B/D > 1.5$, and further preferably $B/D > 2.0$.

[0067] However, as will be described just in case, the above “trade-off relationship” does not mean that it is always realized in principle, but means that there is a trade-off relationship in many cases on the premise of the steel sheet production step by cold rolling and annealing (recrystallization) and magnetic characteristics required for electrical steel sheets. That is, for example, a phenomenon in which the $\{111\} \langle 211 \rangle$ orientation and the $\{411\} \langle 011 \rangle$ orientation simultaneously increase or decrease is not denied.

[0068] When the $\{111\} \langle 211 \rangle$ orientation strengths (A), (B), and the $\{411\} \langle 011 \rangle$ orientation strengths (C), (D) of the base steel sheets of the core material of the stator and the core material of the rotor respectively satisfy the relationship of $B/A > 1.0$ and the relationship of $C/D > 1.0$, the reason why the motor noise is reduced is considered to be as follows, for example.

[0069] As described above, since the $\{411\} \langle 011 \rangle$ orientation is a preferred orientation for magnetic characteristics, in the conventional electrical steel sheet for a motor, control to increase the strength of this orientation has been performed. However, since this orientation has large in-plane anisotropy of Young's modulus, when an electrical steel sheet having high $\{411\} \langle 011 \rangle$ orientation strength is used as the core material of the rotor, the electrical steel sheet is deformed non-isotropically with respect to a rotating shaft during rotation, and vibration is generated to increase noise.

[0070] As in the rotary electric machine according to the present embodiment, the non-oriented electrical steel sheet having high $\{411\} \langle 011 \rangle$ orientation strength is used only as the core material of the stator, and the non-oriented electrical steel sheet having relatively low $\{411\} \langle 011 \rangle$ orientation strength and increased $\{111\} \langle 211 \rangle$ orientation strength with small in-plane anisotropy of Young's modulus is used as the core material of the rotor. As a result, deformation during rotation is isotropic with respect to the rotating shaft, so that vibration is suppressed to reduce noise.

[0071] In the non-oriented electrical steel sheet that is the core material of the rotor of the rotary electric machine according to the present embodiment, it is preferable that the $\{111\} \langle 211 \rangle$

orientation strength (B) and the $\{111\} \langle 011 \rangle$ orientation strength (E) further satisfy a relationship of $B/E > 1.0$.

[0072] In the present embodiment, the $\{411\} \langle 011 \rangle$ orientation having large in-plane anisotropy and the $\{111\} \langle 211 \rangle$ orientation having small in-plane anisotropy are controlled, but as for the $\{111\}$ orientation, the $\{111\} \langle 011 \rangle$ orientation is likely to develop in addition to the $\{111\} \langle 211 \rangle$ orientation. Considering the overall influence of these orientations on the in-plane anisotropy, regarding the $\{111\}$ orientation, the $\{111\} \langle 011 \rangle$ orientation having the same in-plane orientation $\langle 011 \rangle$ as the $\{410\} \langle 011 \rangle$ orientation is disadvantageous for reducing the overall in-plane anisotropy more than the $\{111\} \langle 211 \rangle$ orientation. From this viewpoint, in the rotary electric machine according to the present embodiment, $B/E > 1.0$ is preferably satisfied in the non-oriented electrical steel sheet included in the rotor. It is more preferably $B/E > 1.5$, and further preferably $B/E > 2.0$.

[0073] In the rotary electric machine according to the present embodiment, in the non-oriented electrical steel sheet that is the core material of the stator, the $\{411\} \langle 011 \rangle$ orientation strength (C) of the base steel sheet and the $\{100\} \langle 011 \rangle$ orientation strength (F) of the base steel sheet preferably satisfy a relationship of $C/F > 1.0$.

[0074] In the $\{100\} \langle 011 \rangle$ orientation, the increase margin of the iron loss is high with respect to compressive stress. There are several methods for fixing the stator, but most of them are methods in which compressive stress is applied to the core of the stator. Therefore, it is better to increase $\{411\} \langle 011 \rangle$ having low compressive stress sensitivity. It is more preferably $C/F > 1.5$, and further preferably $C/F > 2.0$.

[Chemical Composition]

[0075] It is preferable that the chemical compositions of the base steel sheets of the non-oriented electrical steel sheet that is the core material of the stator and the non-oriented electrical steel sheet that is the core material of the rotor of the rotary electric machine according to the present embodiment are the following chemical compositions, respectively, as the core material of the stator and the core material of the rotor that satisfy each orientation strength requirement can be obtained from the manufactured non-oriented electrical steel sheet. “%” in the description of the chemical composition means “mass %”.

[0076] In the rotary electric machine according to the present embodiment, the non-oriented electrical steel sheet that is the core material of the stator and the non-oriented electrical steel sheet that is the core material of the rotor may have the same chemical composition of the base steel sheet, but may have different chemical compositions as described later.

(C: 0.0100% or Less)

[0077] C is an element that increases iron loss or causes magnetic aging. Therefore, the lower the C content, the more preferable. Such a phenomenon is remarkable when the C content is more than 0.0100%. Therefore, the C content is set to 0.0100% or less. The reduction of the C content also contributes to uniform improvement of magnetic characteristics in all directions in the sheet surface. The lower limit of the C content is not particularly limited, but is preferably set to 0.0005% or more in consideration of the cost of decarburization treatment at the time of refining.

(Si: 0.5000 to 4.0000%)

[0078] Si is an element that increases electric resistance, reduces eddy-current loss, reduces iron loss, or increases yield ratio to improve punching workability into a core. When the Si content is less than 0.5000%, these effects cannot be sufficiently obtained. Therefore, the Si content is set to 0.5000% or more. The Si content is preferably 0.9000% or more, and more preferably 1.5000% or more. On the other hand, when the Si content is more than 4.0000%, the magnetic flux density decreases, punching workability decreases or cold rolling becomes difficult due to an excessive increase in hardness. Therefore, the Si content is set to 4.0000% or less.

[0079] Also, Si is an element contained in a relatively large amount in the electrical steel sheet, and has a large effect on the $\{111\} \langle 211 \rangle$ orientation and the $\{411\} \langle 011 \rangle$ orientation after the cold

rolling and the recrystallization annealing mainly controlled in the present embodiment. In low Si steel, the {111} <211> orientation is likely to develop, and the {411} <011> orientation is likely to be suppressed.

[0080] Therefore, it is preferable that the non-oriented electrical steel sheet used as the core material of the stator has a larger amount of Si in the base steel sheet than the non-oriented electrical steel sheet used as the core material of the rotor. In particular, the presence or absence of transformation due to the Si content in the steel sheet production step can be utilized for the control of the texture, and it is further preferable that the steel sheet used for the core material of the stator has a non-transformational chemical composition of high Si, and the steel sheet used for the core material of the rotor has a transformational chemical composition of low Si.

(Sol.Al: 0.0001 to 1.0000%)

[0081] Al is an element that increases electric resistance, reduces eddy-current loss, and reduces iron loss. Al also contributes to improvement of the relative magnitude of the magnetic flux density B₅₀ with respect to the saturation magnetic flux density. When the sol.Al (acid-soluble Al) content is less than 0.0001%, these operation and effects cannot be sufficiently obtained. Al also has an effect of promoting desulfurization in steelmaking. Therefore, the sol.Al content is set to 0.0001% or more. On the other hand, when the sol.Al content is more than 1.0000%, the magnetic flux density decreases, the yield ratio decreases, and the punching workability decreases. Therefore, the sol.Al content is set to 1.0000% or less.

[0082] Here, the magnetic flux density B₅₀ is a magnetic flux density in a magnetic field of 5000 A/m.

(S: 0.0100% or Less)

[0083] S is not an essential element, and is, for example, an element contained in steel as an impurity. S is precipitated as fine MnS, thereby inhibiting recrystallization and grain growth in annealing. Therefore, the lower the S content, the more preferable. Such increase in iron loss and decrease in magnetic flux density due to the inhibition of recrystallization and grain growth are remarkable when the S content is more than 0.0100%. Therefore, the S content is set to 0.0100% or less. The lower limit of the S content is not particularly limited, but is preferably set to 0.0003% or more in consideration of the cost of desulfurization treatment at the time of refining.

(N: 0.0100% or Less)

[0084] Like C, N is an element that deteriorates magnetic characteristics. Therefore, the lower the N content, the more preferable. When the N content is more than 0.0100%, the adverse effect becomes significant, and thus the N content is set to 0.0100% or less. The lower limit of the N content is not particularly limited, but is preferably set to 0.0010% or more in consideration of the cost of denitrification treatment at the time of refining.

(One or More Selected from the Group Consisting of Mn, Ni, Co, Pt, Pb, Cu, and Au: 0.1000 to 5.0000% in Total)

[0085] It is necessary to contain at least one or more of elements Mn, Ni, Co, Pt, Pb, Cu, and Au in an amount of 0.1000% or more in total. In addition, the amount of at least one or more of these elements is more preferably set to 0.2000% or more in total from the viewpoint of increasing the electric resistance and decreasing the iron loss. The content is further preferably 1.0000% or more in total.

[0086] On the other hand, when the amount of these elements exceeds 5.0000% in total, the cost increases, and the magnetic flux density may decrease. Therefore, the amount of at least one of these elements is set to 5.0000% or less in total. The amount is preferably 4.0000% or less.

(Cr: 0 to 2.0000%)

[0087] Cr is an element that improves corrosion resistance, high frequency characteristics, and texture. Cr does not need to be contained, and the lower limit of the Cr content is 0%. The effect of containing Cr can be obtained even in a trace amount, but in order to reliably obtain the effect of containing Cr, the content is set to preferably 0.0010% or more, more preferably 0.0020% or more,

further preferably 0.0200% or more, and still more preferably 0.1000% or more.

[0088] On the other hand, when the Cr content is more than 2.0000%, Cr forms a carbonitride, the carbonitride refines grain size, and the iron loss increases. Therefore, the Cr content is set to 2.0000% or less.

(Sn: 0 to 0.4000%, Sb: 0 to 0.4000%, P: 0 to 0.4000%)

[0089] Sn and Sb are elements that improve the texture after cold rolling and recrystallization to improve the magnetic flux density. Therefore, these elements can be contained as necessary. In order to improve magnetic characteristics and the like, it is preferable to contain one or more selected from the group consisting of 0.0200 to 0.4000% of Sn, 0.0200 to 0.4000% of Sb, and 0.0200 to 0.4000% of P.

[0090] On the other hand, when Sn and Sb are excessively contained, the steel embrittles. Therefore, the Sn content and the Sb content are both set to 0.4000% or less. In addition, P can be contained in order to ensure the hardness of the steel sheet after recrystallization, but if P is excessively contained, embrittlement of the steel is caused. Therefore, the P content is set to 0.4000% or less.

(Ti: 0 to 0.1000%, Nb: 0 to 0.1000%)

[0091] Ti and Nb are elements that change the texture after cold rolling and recrystallization by fixing and reducing solute C and solute N as precipitates. By containing Ti and Nb, they act to increase the {111} <211> orientation strength, and lower the {411} <011> orientation strength. In order to sufficiently obtain this effect, it is preferable to contain Ti and Nb in an amount equal to or more than the equivalent of the C content and the N content, and in general, each of Ti and Nb is contained in an amount of 0.0200% or more, and further preferably 0.0400% or more.

[0092] However, the Ti content and the Nb content are both set to 0.1000% or less.

[0093] As described above, the {111} <211> orientation strength increases, and the {411} <011> orientation strength decreases by containing Ti and Nb. Therefore, it is preferable that Ti and Nb are contained more in the non-oriented electrical steel sheet as the core material of the rotor.

[0094] However, as described later, when Ti and/or Nb is contained in an amount of 0.0100% or more, sufficient characteristics cannot be obtained unless the temperature rising rate of final annealing is increased to 100° C./sec or more in the case of performing a final annealing process. If the temperature rising rate is not set as described above, the {411} <011> orientation does not develop, which is not preferable. That is, when Ti and/or Nb is contained, manufacturability is deteriorated. Therefore, from this point of view, the Ti content is preferably less than 0.0100%, and the Nb content is preferably less than 0.0100%. More preferably, the total of the Ti content, the Nb content, and the V content and the Zr content to be described later is less than 0.0100%.

Zr: 0 to 0.1000%

V: 0 to 0.1000%

[0095] The chemical composition of the base steel sheet of the non-oriented electrical steel sheet according to the present embodiment may further contain V and/or Zr as an optional element in addition to the above elements.

[0096] Zr and V are both elements having an effect of suppressing recrystallization, increasing the {111} <211> orientation strength, and decreasing the {411} <011> orientation strength. In the case of obtaining this effect, each of the Zr content and the V content is preferably 0.0100% or more.

[0097] On the other hand, when the Zr content and the V content are more than 0.1000%, the steel becomes brittle. Therefore, both the Zr content and the V content are set to 0.1000% or less. The content is preferably 0.0500% or less, and more preferably less than 0.0100%.

[0098] In the rotary electric machine according to the present embodiment, when the Nb content, the Zr content, the Ti content, the V content, the C content, and the N content in mass % of the base steel sheet of the non-oriented electrical steel sheet included in the stator are denoted by Nb.sub.s, Zr.sub.s, Ti.sub.s, V.sub.s, C.sub.s, and N.sub.s, it is preferable to satisfy

$$0 \geq \text{Nb.sub.s}/93 + \text{Zr.sub.s}/91 + \text{Ti.sub.s}/48 + \text{V.sub.s}/51 - (\text{C.sub.s}/12 + \text{N.sub.s}/14).$$

[0099] In this case, an effect of increasing the $\{411\} \langle 011 \rangle$ orientation strength can be obtained.

[0100] The lower limit value is not particularly limited, but may be, for example,

$\text{Nb.sub.s}/93 + \text{Zr.sub.s}/91 + \text{Ti.sub.s}/48 + \text{V.sub.s}/51 - (\text{C.sub.s}/12 + \text{N.sub.s}/14) \geq -1.55 \times 10^{-3}$.

[0101] In addition, when the Nb content, the Zr content, the Ti content, the V content, the C content, and the N content in mass % of the base steel sheet of the non-oriented electrical steel sheet included in the rotor are denoted by Nb.sub.r, Zr.sub.r, Ti.sub.r, V.sub.r, C.sub.r, and N.sub.r, respectively, it is preferable to satisfy $0 < \text{Nb.sub.r}/93 + \text{Zr.sub.r}/91 + \text{Ti.sub.r}/48 + \text{V.sub.r}/51 - (\text{C.sub.r}/12 + \text{N.sub.r}/14) < 5.0 \times 10^{-3}$.

[0102] In this case, an effect of increasing the $\{111\} \langle 211 \rangle$ orientation strength can be obtained.

[0103] The remainder of the chemical composition other than the above is Fe and impurities. In the present embodiment, the impurity refers to an element that is mixed from a raw material or in the production step and does not clearly affect the characteristics of the rotary electric machine according to the present embodiment.

[0104] Examples of the impurities include B, O, Mg, Ca, Nd, Bi, W, Mo, and Y in addition to the above-described elements. The contents of these elements are each preferably, for example, 0.10% or less. In addition, the amount of all impurities is preferably 5.00% or less, and more preferably 1.00% or less in total.

[0105] In the rotary electric machine according to the present embodiment, the chemical composition of the base steel sheet of the non-oriented electrical steel sheet included in the stator and the chemical composition of the base steel sheet of the non-oriented electrical steel sheet included in the rotor may be the same, but in consideration of the above effect, when the Si content, the Ti content, and the Nb content in mass % of the base steel sheet of the non-oriented electrical steel sheet included in the stator are respectively denoted by Si.sub.s, Ti.sub.s, and Nb.sub.s, and the Si content, the Ti content, and the Nb content of the base steel sheet of the non-oriented electrical steel sheet included in the rotor are respectively denoted by Si.sub.r, Ti.sub.r, and Nb.sub.r, it is preferable that any one of $\text{Si.sub.s}/\text{Si.sub.r} > 1.0$, $\text{Ti.sub.r}/\text{Ti.sub.s} > 1.0$, and $\text{Nb.sub.r}/\text{Nb.sub.s} > 1.0$ is satisfied.

[0106] When any one of $\text{Si.sub.s}/\text{Si.sub.r} > 1.0$, $\text{Ti.sub.r}/\text{Ti.sub.s} > 1.0$, and $\text{Nb.sub.r}/\text{Nb.sub.s} > 1.0$ is satisfied, an effect in which the motor loss is further reduced can be obtained.

[0107] In the rotary electric machine according to the present embodiment, difference in a total of the Si content, the Mn content, and the sol.Al content in the base steel sheets between the non-oriented electrical steel sheet included in the stator and the non-oriented electrical steel sheet included in the rotor is preferably within 0.20 mass % (the absolute value of the difference is 0.20 mass % or less). In this case, there is an advantage that work efficiency and cost can be reduced including a case where the stator and the rotor are prepared from the same material.

[0108] The chemical composition of the base steel sheet is determined by the following method.

[0109] The entire surface of a test material is polished with a grinder or the like, and the test material washed with acetone is cut with a nibbler or the like to prepare a sample. C and S are measured by combustion-infrared absorption method. N is measured by inert gas fusion-thermal conductivity method. Sol.Al is measured by acid dissolution-ICP emission spectrometry. O is measured by inert gas fusion-non-dispersive infrared absorption method. Other elements are measured by ICP emission spectrometry.

[0110] Here, the insulating coating on the surface may be removed by machining such as polishing as described above, or may be chemically removed using hot alkali.

[0111] In addition, in the case of obtaining the chemical compositions of the base steel sheets of the non-oriented electrical steel sheet included in the stator and the non-oriented electrical steel sheet included in the rotor in the rotary electric machine, the chemical composition may be measured in the manner described above after the non-oriented electrical steel sheet is taken out from the stator or the rotor by disassembling the rotary electric machine.

[0112] Although the detailed method of disassembling the rotary electric machine is different

according to each actual rotary electric machine, for example, first, the rotary electric machine is taken out from the machine including the rotary electric machine. Thereafter, a part of the housing (case) of the rotary electric machine is removed by machining. Then, the stator and the rotor are separated. When there is a permanent magnet in the rotor at this time, it is desirable to insert a spacer such as a plastic sheet between the stator and the rotor because magnetic attraction force is generated. Thereafter, the stator is removed from the housing.

[0113] Since the stator has windings, the windings are removed or partially cut. Excluding a steel sheet at the top of the lamination of the stators or a steel sheet that has been damaged when the winding has been cut, a sample is collected from other places. In many cases, the lamination is fastened by interlocking or welding. In the case of interlocking, it is possible to divide the lamination by, for example, inserting a cutter blade into a gap between the stacked steel sheets. In the case of welding, it is possible to divide the lamination by cutting a welded portion with a hand grinder or the like.

[0114] The rotor often has a coil end made of a material other than an electrical steel sheet. Therefore, the rotor is separated into two by machining using a non-magnetic blade near the longitudinal center of the rotor. Thereafter, the lamination is divided in the same manner as the stator described above. At that time, it is desirable to exclude a portion affected by machining.

[Average Grain Size of Base Steel Sheet]

[0115] In the rotary electric machine according to the present embodiment, the average grain size of the base steel sheet of the non-oriented electrical steel sheet included in the stator is preferably larger than the average grain size of the base steel sheet of the non-oriented electrical steel sheet included in the rotor.

[0116] In this case, an effect that the $\{111\} \langle 211 \rangle$ orientation strength is larger in the rotor and the $\{411\} \langle 011 \rangle$ orientation strength is larger in the stator is obtained.

[0117] The average grain size can be determined by the following method.

[0118] As the average grain size, an average value of grain sizes measured by a cutting method in the sheet thickness direction and the rolling direction may be used in a longitudinal cross-sectional microstructure photograph. As the longitudinal cross-section microstructure photograph, an optical microscope photograph can be used, and for example, a photograph taken at a magnification of 50 times may be used. In the sheet thickness direction, it is preferable to draw 20 or more line segments corresponding to the total length of the sheet thickness and count grain sizes. In the rolling direction, it is preferable to draw line segments with a length of 2 mm at $\frac{1}{4}$, $\frac{1}{2}$, and $\frac{3}{4}$ of the sheet thickness in parallel and count grain sizes.

[0119] However, when a non-recrystallized region is included, only the recrystallized region may be calculated by the above method.

[0120] In the rotary electric machine according to the present embodiment, the non-oriented electrical steel sheet included in the stator is preferably a steel sheet obtained by further performing heat treatment at 600° C. or higher on the non-oriented electrical steel sheet included in the rotor.

[0121] In this case, since the strain introduced by processing is removed, the magnetic characteristics are improved, and the motor characteristics are improved by improving the magnetic characteristics of the stator which is easily affected by the magnetic characteristics of the core material.

[Thickness of Base Steel Sheet]

[0122] Next, the thickness of the base steel sheet of the non-oriented electrical steel sheet according to the present embodiment will be described. The thickness of the base steel sheet of the non-oriented electrical steel sheet according to the present embodiment is not necessarily limited, but is preferably 0.50 mm or less. When the thickness is more than 0.50 mm, it is difficult to obtain excellent high-frequency iron loss. The thickness is preferably 0.35 mm or less, more preferably 0.20 mm or less, and further preferably 0.15 mm or less because it is more advantageous if the sheet thickness is thin from the viewpoint of iron loss.

[0123] On the other hand, from the viewpoint of facilitating the manufacture, the thickness of the base steel sheet of the non-oriented electrical steel sheet according to the present embodiment is preferably 0.10 mm or more.

[Insulating Coating]

[0124] In the non-oriented electrical steel sheet according to the present embodiment, an insulating coating is formed on a surface of the base steel sheet. This insulating coating may be a known coating. For example, a coating film made of Al.sub.2O.sub.3 is an exemplary example.

<Laminated Core>

[0125] The laminated core according to the present embodiment is a laminated core (stator core) formed by laminating the non-oriented electrical steel sheets (the non-oriented electrical steel sheets according to the present embodiment) including a base steel sheet; and an insulating coating formed on a surface of the base steel sheet, the base steel sheet having a chemical composition including, in mass %, C: 0.0100% or less, Si: 0.5000 to 4.0000%, sol.Al: 0.0001 to 1.0000%, S: 0.0100% or less, N: 0.0100% or less, one or more selected from the group consisting of Mn, Ni, Co, Pt, Pb, Cu, and Au: 0.1000 to 5.0000% in total, Cr: 0 to 2.0000%, Sn: 0 to 0.4000%, Sb: 0 to 0.4000%, P: 0 to 0.4000%, Ti: 0 to 0.1000%, Nb: 0 to 0.1000%, Zr: 0 to 0.1000%, V: 0 to 0.1000%, and the remainder of Fe and impurities, and the {111} <211> orientation strength is less than 15, and the {411} <011> orientation strength is 2 to 50, or a laminated core (rotor core) formed by laminating the non-oriented electrical steel sheets (the non-oriented electrical steel sheets according to the present embodiment) including a base steel sheet; and an insulating coating formed on a surface of the base steel sheet, the base steel sheet having a chemical composition including, in mass %, C: 0.0100% or less, Si: 0.5000 to 4.0000%, sol.Al: 0.0001 to 1.0000%, S: 0.0100% or less, N: 0.0100% or less, one or more selected from the group consisting of Mn, Ni, Co, Pt, Pb, Cu, and Au: 0.1000 to 5.0000% in total, Cr: 0 to 2.0000%, Sn: 0 to 0.4000%, Sb: 0 to 0.4000%, P: 0 to 0.4000%, Ti: 0 to 0.1000%, Nb: 0 to 0.1000%, Zr: 0 to 0.1000%, V: 0 to 0.1000%, and the remainder of Fe and impurities, and the {111} <211> orientation strength is 2 to 30, and the {411} <011> orientation strength is 1 to 40.

[0126] The laminated core is manufactured by punching, laminating, and bonding the non-oriented electrical steel sheets according to the present embodiment. In this step, the chemical composition and the texture are not changed. Therefore, the non-oriented electrical steel sheet included in the laminated core has the same chemical composition and texture as those of the non-oriented electrical steel sheet according to the present embodiment described above.

[0127] As can also be seen from this, the chemical composition and texture of the laminated core described above are the chemical composition and texture of the portion that has been the base steel sheet of the non-oriented electrical steel sheet.

[0128] Also, a motor core can be formed by combining the stator core and the rotor core.

[Manufacturing Method]

[0129] Methods for manufacturing the non-oriented electrical steel sheet according to the present embodiment, the laminated core according to the present embodiment, and the rotary electric machine according to the present embodiment will be described.

<Method for Manufacturing Non-Oriented Electrical Steel Sheet>

[0130] First, as the method for manufacturing the non-oriented electrical steel sheet according to the present embodiment, methods for manufacturing the non-oriented electrical steel sheet that is the core material of the rotor and the non-oriented electrical steel sheet that is the core material of the stator will be described.

[0131] A non-oriented electrical steel sheet having predetermined {111} <211> orientation strength and {411} <011> orientation strength (the non-oriented electrical steel sheet that is the core material of the rotor and the non-oriented electrical steel sheet that is the core material of the stator are different in ranges of preferred orientation strength) can be obtained by controlling various conditions in the production step.

[0132] As a first example, an example of a manufacturing method for separately producing a non-oriented electrical steel sheet preferable as the core material of the stator and a non-oriented electrical steel sheet preferable as the core material of the rotor by using slabs having the same chemical composition and changing manufacturing conditions after hot rolling will be described.

[0133] The non-oriented electrical steel sheet according to the present embodiment is manufactured by performing hot rolling and cold rolling, further performing intermediate annealing, skin pass rolling, final annealing, and stress relieving annealing as necessary to manufacture a base steel sheet, and forming an insulating coating on the surface of the base steel sheet after any of the above-described steps.

[0134] A non-oriented electrical steel sheet having predetermined $\{111\} \langle 211 \rangle$ orientation strength and $\{411\} \langle 011 \rangle$ orientation strength can be obtained by controlling various conditions in the production step, and a non-oriented electrical steel sheet preferable as the core material of the stator and a non-oriented electrical steel sheet preferable as the core material of the rotor can be separately produced by whether or not intermediate annealing, skin pass rolling, and final annealing are performed or the like. Here, the intermediate annealing is annealing performed between cold rolling and skin pass rolling, and the final annealing refers to annealing performed after skin pass rolling. This final annealing may be performed by a steel sheet manufacturer or may be performed after core punching by a motor manufacturer (processing manufacturer).

[0135] First, a steel material having the above-described chemical composition is heated and hot-rolled. The steel material is, for example, a slab manufactured by normal continuous casting.

[0136] The heating temperature of the steel material is not limited, but for example, a standard condition of 1000 to 1350° C. can be adopted.

[0137] The rough rolling and the finish rolling of the hot rolling are performed at a temperature equal to or higher than A.sub.r1 temperature. That is, hot rolling is preferably performed such that the temperature at the time of passing through a final pass of finish rolling (finishing temperature) is equal to or higher than the A.sub.r1 temperature. As a result, the crystal structure is refined by transformation from austenite (gamma iron) to ferrite (alpha iron) by subsequent cooling. When cold rolling is then performed in a state where the crystal structure is refined, bulging recrystallization (a phenomenon in which a recrystallized grain grows so as to bulge to a non-recrystallized portion, hereinafter, may be referred to as “bulging”) is likely to occur, and grains of the $\{411\} \langle 011 \rangle$ orientation which are usually difficult to grow can be easily grown. In the non-oriented electrical steel sheet according to the present embodiment, the A.sub.r1 temperature is determined from a change in thermal expansion of the steel material (base steel sheet) during cooling at an average cooling rate of 1° C./sec after being heated to A.sub.c3 temperature. Also, in the steel sheet used in the present invention, the A.sub.c1 temperature (the temperature at which the steel sheet transforms into γ phase) is determined from the change in thermal expansion of the steel material (steel sheet) during heating at an average heating rate of 1° C./sec.

[0138] However, when the chemical composition is non-transformational, the finishing temperature is desirably 850° C. or higher. This is because when the finishing temperature is lower than 850° C., it is difficult to control the shape of the steel sheet during hot rolling.

[0139] Thereafter, the hot-rolled steel sheet is coiled up without performing hot-band annealing. When hot-band annealing is performed, the $\{411\} \langle 011 \rangle$ orientation cannot be enriched in a later step. The temperature at the time of coiling is not limited, but is preferably higher than 250° C. and 700° C. or lower. By coiling the hot-rolled steel sheet after hot rolling at a temperature higher than 250° C. and 700° C. or lower, it is possible to obtain the effect that the crystal structure before cold rolling can be refined and the $\{411\} \langle 011 \rangle$ orientation having excellent magnetic characteristics can be enriched at the time of recrystallization. The temperature at the time of coiling is more preferably 400 to 600° C., and further preferably 400 to 480° C.

[0140] Thereafter, the hot-rolled steel sheet is subjected to pickling and cold rolling. In the cold rolling, it is preferable to set the rolling reduction to 80.0 to 92.0%. As the rolling reduction is

higher, the grains having the $\{411\} \langle 011 \rangle$ orientation are more likely to grow by the subsequent recrystallization.

[0141] On the other hand, when the rolling reduction exceeds 92.0%, the load in cold rolling increases, leading to an increase in cost.

[0142] The rolling reduction of the cold rolling is determined so as to obtain a necessary product sheet thickness after the skin pass rolling in consideration of the skin pass rolling described later.

[0143] After completion of the cold rolling, intermediate annealing is subsequently performed. The intermediate annealing may not be performed. When the intermediate annealing is performed, the recrystallization ratio is set to 1 to 99%, and preferably 50 to 99% by controlling the temperature of intermediate annealing to be lower than the A.sub.c1 temperature.

[0144] If the temperature of intermediate annealing is too low, there is a concern that bulging does not sufficiently occur and grains of the $\{411\} \langle 011 \rangle$ orientation do not sufficiently grow.

Therefore, the temperature of intermediate annealing is preferably set to 600° C. or higher. In addition, when the temperature of intermediate annealing becomes equal to or higher than the A.sub.c1 temperature, austenite transformation occurs during annealing, the frequency of occurrence of grains having a crystal orientation other than the $\{411\} \langle 011 \rangle$ orientation increases, and the inventive effect may be impaired. Therefore, the intermediate annealing is performed at a temperature lower than the A.sub.c1 temperature. When the chemical composition is non-transformational, the intermediate annealing temperature is set to 800° C. or lower. The time of such intermediate annealing is preferably 5 to 60 seconds.

[0145] The recrystallization ratio is preferably 50% or more at the time point after the intermediate annealing since the $\{411\} \langle 011 \rangle$ orientation grains are more likely to grow after the final annealing or the stress relieving annealing.

[0146] The recrystallization ratio of the steel sheet after intermediate annealing (cold-rolled steel sheet to be a base steel sheet of the non-oriented electrical steel sheet) can be specified by the following procedure.

[0147] First, a sample collected from the steel sheet is polished from the surface so as to have a sheet thickness of $\frac{1}{2}$ (so as to expose the center of the sheet thickness), and the polished surface is observed by an electron back scattering diffraction (EBSD) method. Then, a grain satisfying any one of the following conditions (a) and (b) is determined as a non-recrystallized portion, and the non-recrystallized rate is calculated by the ratio of the area of the non-recrystallized portion to the area of the entire observed visual field. [0148] (a) Grains having a grain size of more than 300 μm . [0149] (b) Grains having an aspect ratio of more than 2, that is, satisfying (length in rolling direction)/(length in 90 degree direction with respect to rolling direction) > 2.

[0150] After completion of the intermediate annealing, skin pass rolling is then performed. The skin pass rolling may not be performed. Also, when the intermediate annealing is not performed, the skin pass rolling is performed after the cold rolling. By performing the skin pass rolling, the $\{111\} \langle 211 \rangle$ orientation strength increases, and a non-oriented electrical steel sheet suitable as the core material of the rotor is obtained.

[0151] The rolling reduction of the skin pass rolling can be determined in a suitable range on the assumption that a steel sheet obtained by further performing final annealing on a steel sheet subjected to skin pass rolling as described later is used as the core material of the stator. As described above, when the steel sheet in which bulging has occurred is slightly rolled and further annealed, the $\{411\} \langle 011 \rangle$ orientation grains occurred by bulging further grow. This is an example of a phenomenon generally known as strain-induced grain boundary migration (hereinafter, sometimes referred to as SIBM). In order to utilize this phenomenon, the rolling reduction of the skin pass rolling is set to 5 to 25%. When the rolling reduction of the skin pass rolling is less than 5%, the amount of strain accumulated in the steel sheet is small, so that SIBM does not occur. On the other hand, when the rolling reduction of the skin pass rolling is more than 25%, not SIBM but recrystallization nucleation occurs because the strain is too large. In nucleation, the frequency of

generation of $\{111\} \langle 211 \rangle$ grains is increased. Thus, if this steel sheet is used as the core material of the stator, the magnetic characteristics of the stator are deteriorated. From the viewpoint of sufficiently obtaining the effect from this viewpoint, the rolling reduction of the skin pass rolling is more preferably set to 5 to 15%.

[0152] In addition, when the rolling reduction (%) in the cold rolling is defined as R_m and the rolling reduction (%) in the skin pass rolling is defined as R_s , it is preferable that the rolling reductions in the cold rolling and the skin pass rolling are adjusted so as to satisfy $86 < R_m + 0.2 \times R_s < 92$ and $5 < R_s < 20$.

[0153] The steel sheet after the skin pass rolling is subsequently subjected to final annealing. The final annealing may not be performed. When the intermediate annealing or the skin pass rolling is not performed, the final annealing is performed on the steel sheet after the cold rolling or after the intermediate annealing.

[0154] In the case of obtaining the effect of final annealing, it is preferable to perform final annealing on the steel sheet after the skin pass rolling. In this case, the strain introduced by the skin pass rolling can be released by the final annealing, and the final annealing can be performed at a temperature and time that occurs recrystallization by the SIBM. The higher the annealing temperature, the shorter the treatment time. However, the α -fwdarw. γ transformation should be avoided, and the upper limit of the temperature is preferably less than the A_{c1} temperature. Specifically, a temperature of 600 to less than $A_{c1}^\circ \text{C}$. is an exemplary example, and a time of more than 0 seconds and 100 hours or less is an exemplary example. In the case of a general continuous annealing furnace, 700 to less than $A_{c1}^\circ \text{C}$. and 1 to 300 seconds can be exemplified, and in the case of a batch annealing furnace, 600 to less than $A_{c1}^\circ \text{C}$. and 20 to 1200 minutes can be exemplified. By appropriately controlling the holding temperature and time, the strain introduced by the skin pass rolling can be sufficiently released by the SIBM, and warpage at the time of punching into a complicated shape can be suppressed. At the same time, grains can be avoided from being too coarse, and a decrease in punching accuracy due to shear drop at the time of punching can be suppressed, that is, workability of the non-oriented electrical steel sheet can be improved.

[0155] When the skin pass rolling is not performed, strain can be sufficiently released by final annealing, so that workability is not deteriorated in the first place.

[0156] Since the steel sheet after final annealing has high $\{411\} \langle 011 \rangle$ orientation strength, the steel sheet becomes a non-oriented electrical steel sheet suitable as the core material of the stator.

[0157] The temperature rising rate of the final annealing is preferably 30°C./sec or more from the viewpoint of increasing the $\{411\} \langle 011 \rangle$ orientation strength. More preferably, it is 100°C./sec or more, or 200°C./sec or more. The temperature rising rate may be 300°C./sec or more, further 400°C./sec or more, or 500°C./sec or more.

[0158] In particular, when the base steel sheet contains 0.010% or more of Ti, Nb, V, or Zr in total, if the temperature rising rate of the final annealing is less than 100°C./sec , the effect of lowering the $\{411\} \langle 011 \rangle$ orientation strength is remarkable, and thus the temperature rising rate is preferably 100°C./sec or more.

[0159] In general stress relieving annealing, even if only the stator is subjected to stress relieving annealing, the $\{411\} \langle 011 \rangle$ orientation strength does not increase so much, and the $\{111\} \langle 011 \rangle$ orientation strength increases. Therefore, it is difficult to satisfy the intended relationship of $B/A > 1.0$ for the $\{111\} \langle 211 \rangle$ orientation strength (A) of the core material of the stator and the $\{111\} \langle 211 \rangle$ orientation strength (B) of the core material of the rotor, and the intended relationship of $C/D > 1.0$ for the $\{411\} \langle 011 \rangle$ orientation strength (C) of the core material of the stator and the $\{411\} \langle 011 \rangle$ orientation strength (D) of the core material of the rotor. On the other hand, in the above method utilizing bulging and SIBM, since the $\{411\} \langle 011 \rangle$ orientation grows by encroaching the $\{111\} \langle 211 \rangle$ orientation by annealing only the stator, it is very convenient to satisfy the intended relationships of $B/A > 1.0$ and $C/D > 1.0$.

[0160] When the non-oriented electrical steel sheet according to the present embodiment is formed into a motor core, forming processing or the like (for example, punching) is performed to obtain a desired core member shape. Then, in order to relief strain or the like generated by forming processing or the like, stress relieving annealing may be performed. The final annealing may be performed as stress relieving annealing for the stator core. The temperature of stress relieving annealing is preferably set to about 800° C., for example, and the time of stress relieving annealing is set to preferably about 2 hours.

[0161] In the non-oriented electrical steel sheet according to the present embodiment, an insulating coating is formed on the surface of the base steel sheet before or after the stress relieving annealing, after the last step among cold rolling, intermediate annealing, skin pass rolling, and final annealing. As the conditions for forming the insulating coating, the same conditions as those for forming the insulating coating of the conventional non-oriented electrical steel sheet may be adopted.

[0162] As another example of separate production of the non-oriented electrical steel sheet that is the core material of the rotor and the non-oriented electrical steel sheet that is the core material of the stator, there is a method of performing hot rolling, cold rolling, intermediate annealing, and skin pass rolling on slabs having the same chemical composition under the same conditions (as the same sheet), and then separately producing depending on whether or not final annealing or stress relieving annealing is performed. In this method, a steel sheet subjected to the skin pass step is manufactured and shipped by a steel sheet manufacturer, and then a core material of a rotor and a core material of a stator are punched out from the same steel sheet (generally referred to as integrated punching or the like) by a motor manufacturer (processing manufacturer), the rotor core is used without performing stress relieving annealing, and the stator core is used after performing stress relieving annealing, whereby the rotary electric machine of the present invention can be manufactured. Since the core material of the rotor and the core material of the stator are separately produced by stress relieving annealing, which is the final stage of manufacturing the motor core, it is convenient in terms of distribution, steel sheet arrangement, and yield, and it can be said that it is a very preferable method from the industrial viewpoint.

[0163] That is, for example, the non-oriented electrical steel sheet included in the stator may be a steel sheet obtained by further performing heat treatment (final annealing or stress relieving annealing) at 600° C. or higher on the non-oriented electrical steel sheet included in the rotor.

[0164] As described above, a core material applicable to the rotary electric machine according to the present embodiment can be obtained.

[0165] The non-oriented electrical steel sheet that is the core material of the rotor and the non-oriented electrical steel sheet that is the core material of the stator of the rotary electric machine according to the present embodiment may be separately produced by a method other than the above. For example, they may be manufactured by using steel materials having different chemical compositions, or also can be separately produced according to hot rolling conditions, cold rolling conditions, and the like.

[0166] For the conditions not described above, known conditions can be appropriately adopted.

[0167] The electrical steel sheet manufactured (non-oriented electrical steel sheet) as described above is an electrical steel sheet suitable as the core material of the stator or the core material of the rotor of the rotary electric machine according to the present embodiment. Basically, a steel sheet manufactured so as to suppress integration in the {111} <211> orientation and promote integration in the {411} <011> orientation is an electrical steel sheet suitable as the core material of the stator, and a steel sheet manufactured so as to promote integration in the {111} <211> orientation is an electrical steel sheet suitable as the core material of the rotor. Furthermore, when the core of the motor is subjected to stress relieving annealing, a steel sheet in which a change in crystal orientation due to the stress relieving annealing is also taken into consideration can be applied. Then, the rotary electric machine according to the present embodiment can be obtained by selecting and using a steel sheet such that the orientation strengths (A), (B), (C), (D), (E), and (F) of the

respective core materials satisfy a predetermined relationship.

[0168] It is necessary to consider that a method of using two types of steel sheets each having a texture separately produced by chemical compositions, hot rolling conditions, hot band heat treatment conditions, cold rolling conditions, final annealing conditions, or the like as the core material of the stator or the core material of the rotor is disadvantageous in terms of steel sheet yield as compared with the method of punching the core material of the stator and the core material of the rotor from one type of steel sheet described above in that it is not so-called integrated punching. However, since the texture of each steel sheet can be completely independently controlled, it is also advantageous in terms of the magnitude of the effect if the steel sheet is appropriately selected.

<Method for Manufacturing Laminated Core>

[0169] Among the non-oriented electrical steel sheets according to the present embodiment described above, the laminated core according to the present embodiment is manufactured using a non-oriented electrical steel sheet in which the {111} <211> orientation strength is less than 15 and the {411} <011> orientation strength is 2 to 50 as a material of a stator core, or a non-oriented electrical steel sheet in which the {111} <211> orientation strength is 2 to 30 and the {411} <011> orientation strength is 1 to 40 as a material of a rotor core.

[0170] Specifically, different non-oriented electrical steel sheets for the stator and for the rotor are prepared, and each steel sheet is processed by punching, and laminated. Alternatively, the same electrical steel sheet may be used for the stator and the rotor, processed by punching, and laminated, and stress relief annealing may be performed only for the stator. Punching and lamination may be performed by known methods.

<Method for Manufacturing Rotary Electric Machine>

[0171] The rotary electric machine according to the present embodiment is manufactured by manufacturing the laminated core, winding the laminated core by a known method, and assembling by housing in a housing. At this time, the order of winding and housing in a housing may be reversed.

EXAMPLES

[0172] Hereinafter, embodiments of the present invention will be further described with reference to examples.

[0173] Conditions used in the examples are examples of conditions for confirmation, and the present invention is not limited to these examples, and various conditions can be adopted without departing from the present invention as long as the object of the present invention is achieved.

(Manufacture of Electrical Steel Sheet)

[0174] Molten steel was cast to prepare ingots, hot rolling, pickling, and cold rolling were performed, and for some examples, one or more steps of intermediate annealing, skin pass rolling, and final annealing were further performed and thereby electrical steel sheets (non-oriented electrical steel sheets) are prepared. The chemical compositions of each kind of steel of the obtained electrical steel sheets and the transformation temperatures of the steel sheets are shown in Table 1. Among the chemical compositions, the contents of impurities not specified in the table were each 0.0010% or less, and 0.10% or less in total. A.sub.r1 (° C.) represents a temperature at which transformation to α phase occurs, and A.sub.c1 (° C) represents a temperature at which transformation to γ phase occurs. The chemical composition that does not undergo α - γ transformation (non-transformational) was described as “-” in the column of phase transformation point temperature. Also, the column of formula.sup.1) in the table shows calculation results of $Nb/93+Zr/91+Ti/48+V/51-(C/12+N/14)$ using contents of Nb, Zr, Ti, V, C, and N in mass %.

[0175] Further, various manufacturing conditions are shown in Table 2-1 and Table 2-2.

[0176] Furthermore, an insulating coating made of known Al.sub.2O.sub.3 was formed on the surface of the electrical steel sheet obtained by the above method. The thickness of the insulating coating was set to 0.5 μ m.

[0177] The final thickness in Table 2 is the thickness of the base steel sheet after the step in Table 2 is completed.

TABLE-US-00001 TABLE 1 Phase trans- Composition (mass %) Remainder Fe and impurities formation Total point of temperature Steel Mn, For A.sub.r1 A.sub.c1 type C Si Mn Ni Co Pt Pb Cu Au etc. P S sol. Al N Cr Others mula.sup.1) (° C.) (° C.) A 0.0023 2.4831 3.2732 — — — — — — — — 3.2732 0.0097 0.0020 0.2994 0.0021 — — -0.00034 800 900 B 0.0022 3.2203 0.4905 — — — — — — — — 0.4905 0.0100 0.0018 0.5979 0.0019 — — -0.00032 — — C 0.0017 3.2149 0.5125 — — — — — — — — 0.5125 0.0103 0.0019 0.6010 0.0022 — Nb: 0.0899 0.00067 — — D 0.0039 0.8959 0.9880 — — — — — — 0.9880 0.0050 0.0017 0.3008 0.0029 — — -0.00053 800 900 E 0.0007 0.8877 1.0079 — — — — — — 1.0079 0.0051 0.0020 0.3012 0.0018 — Ti: 0.0051 -0.00008 800 900 F 0.0019 2.5064 3.3202 — — — — — — 3.3202 0.0098 0.0023 0.2976 0.0018 — Sn: 0.1023 -0.00028 800 900 G 0.0020 2.4985 3.3273 — — — — — — 3.3273 0.0103 0.0019 0.3021 0.0017 — Sb: 0.1035 -0.00029 800 900 H 0.0021 2.5221 3.2718 — — — — — — 3.2718 0.0098 0.0017 0.3013 0.0018 0.0019 — -0.00030 800 900 I 0.0018 2.5226 — 3.3252 — — — — — 3.3252 0.0103 0.0019 0.3010 0.0017 0.0022 — -0.00027 800 900 J 0.0022 2.5134 — — 3.3495 — — — — 3.3495 0.0102 0.0021 0.3010 0.0019 0.0020 — -0.00032 800 900 K 0.0022 2.5130 — — — 3.3006 — — — 3.3006 0.0101 0.0020 0.3013 0.0020 0.0023 — -0.00033 800 900 L 0.0018 2.5028 — — — 3.3069 — — 3.3069 0.0101 0.0020 0.3002 0.0021 0.0022 — -0.00030 800 900 M 0.0023 2.4731 — — — 3.3152 — 3.3152 0.0101 0.0018 0.3029 0.0018 0.0019 — -0.00032 800 900 N 0.0019 2.4723 — — — 3.3528 3.3528 0.0098 0.0020 0.3007 0.0021 0.0018 — -0.00030 800 900 O 0.0098 2.4946 3.3000 — — — — — 3.3000 0.0098 0.0019 0.2976 0.0018 0.0020 — -0.00094 750 950 P 0.0018 2.5235 3.3256 — — — — — 3.3256 — 0.0022 0.2972 0.0019 0.0019 — -0.00028 800 900 Q 0.0017 2.5027 3.2849 — — — — — 3.2849 0.3501 0.0021 0.3000 0.0019 0.0022 — -0.00028 750 950 R 0.0020 2.4946 3.2805 — — — — — 3.2805 0.0099 0.0091 0.2999 0.0017 0.0017 — -0.00029 800 900 S 0.0020 2.5037 3.2733 — — — — — 3.2733 0.0101 0.0021 0.8999 0.0023 0.0021 — -0.00032 820 880 T 0.0018 2.5130 3.3241 — — — — — 3.3241 0.0098 0.0018 0.3027 0.0090 0.0022 — -0.00079 800 900 U 0.0021 2.5198 3.3155 — — — — — 3.3155 0.0103 0.0022 0.2973 0.0018 2.0000 — -0.00031 750 950 V 0.0010 0.8832 0.9954 — — — — — 0.9954 0.0051 0.0018 0.3029 0.0018 — V: 0.0299 0.00038 800 900 W 0.0008 0.9018 1.0019 — — — — — 1.0019 0.0048 0.0021 0.2992 0.0022 — Zr: 0.0302 0.00011 800 900 .sup.1)Nb/93 + Zr/91 + Ti/48 + V/51-(C/12 + N/14)

TABLE-US-00002 TABLE 2-1 Hot- Skin Hot rolling rolled Cold pass Heating Finishing Coiling steel rolling Intermediate rolling Final annealing Final Steel temper- temper- temper- sheet Rolling annealing Rolling Temper- Temperature thick- sheet Steel ature ature ature thickness reduction Temperature Time reduction ature Time rising rate ness No. type (° C.) (° C.) (° C.) mm (%) (° C.) (sec) (%) (° C.) (sec) (° C./s) mm A1 A 1150 800 700 2.5 84.6 700 30 9 — — — 0.35 A2 A 1150 800 700 2.5 84.6 700 30 9 800 30 500 0.35 A3 A 1150 800 700 2.5 84.6 — — 9 — — — 0.35 A4 A 1150 800 550 2.5 84.6 700 30 9 — — — 0.35 A5 A 1150 800 450 2.5 84.6 700 30 9 — — — 0.35 A6 A 1150 800 700 2.5 84.6 700 30 9 800 30 30 0.35 A7 A 1150 800 700 2.5 84.6 700 30 9 800 30 120 0.35 B1 B 1200 900 700 1.8 88.9 — — — 950 60 500 0.20 B2 B 1200 900 700 1.8 87.7 800 30 10 950 60 500 0.20 B3 B 1200 900 700 1.8 88.9 — — — 950 60 800 0.20 C1 C 1150 900 700 1.8 88.9 — — — 950 60 500 0.20 C2 C 1150 900 700 1.8 88.9 — — — 950 60 30 0.20 D1 D 1150 800 700 2.5 84.6 700 30 9 — — — 0.35 D2 D 1150 800 700 2.5 84.6 700 30 9 800 30 500 0.35 D3 D 1150 800 700 2.5 84.6 — — 9 — — — 0.35

TABLE-US-00003 TABLE 2-2 Hot- Skin Hot rolling rolled Cold pass Final annealing Heating Finishing Coiling steel rolling Intermediate rolling Temper- Final Steel temper- temper- temper- sheet Rolling annealing Rolling Temper- ature thick- sheet Steel ature ature ature thickness reduction Temperature Time reduction ature Time rising rate ness No. type (° C.) (° C.) (° C.) mm (%) (° C.) (sec) (%) (° C.) (sec) (° C./s) mm E1 E 1150 900 650 2.5 84.6 — — 9 850 60 500 0.35 E2

E 1150 900 650 2.5 84.6 — — 9 850 60 30 0.35 F1 F 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 G1 G 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 H1 H 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 I1 I 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 J1 J 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 K1 K 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 L1 L 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 M1 M 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 N1 N 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 O1 O 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 P1 P 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 Q1 Q 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 R1 R 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 S1 S 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 T1 T 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 U1 U 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 V1 V 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35 W1 W 1150 800 700 2.5 84.6 700 30 9 850 60 500 0.35

(Manufacture and Evaluation of Motor)

[0178] Next, using the obtained electrical steel sheet, a stator core and a rotor core used for the motor for evaluation were manufactured. At that time, as shown in Tables 3-1 to 3-4, some cores were subjected to stress relieving annealing at 800° C. for 2 hours. Then, these cores were combined to manufacture a motor for evaluation, and motor loss and noise were measured.

(Motor for Evaluation)

[0179] FIG. 1 is a partial plan view of a motor. A motor 300 is an IPM motor prepared based on the Institute of Electrical Engineers of Japan D-model. The outer diameter of a stator core 3 is 112 mm (=54 mm+0.5 mm×2+28.5 mm×2), the outer diameter of a rotor 302 is 54 mm, and the stack height of the stator core 3 is 100 mm. The number of slots is 24. The stator core 3 is fixed to a housing 301 by shrink fitting. The inner diameter of the stator core 3 is 55 mmφ, and the gap between the rotor 302 and the stator core 3 is 0.5 mm. The stator core has 24 slots, the number of windings per phase of a copper wire wound around a teeth of the stator core is 35 turns, and magnetic flux density Br of a rotor magnet is 1.25 T.

(Motor Loss)

(Noise)

[0180] In the present example, loss (motor loss (W)) and noise generated in the motor when a winding current with a peak value of 3A was passed at α phase angle of 30 degrees and the motor was driven at a rotation speed of 1500 RPM for 60 minutes were obtained.

[0181] The power (W) required under the above operating conditions and the work (W) done by the motor were obtained, and the loss of the motor was obtained by power-work. The power was measured using a power meter. As the work, a torque meter was attached at the tip of the motor, and the work was obtained from torque×rotation speed. Noise measurement was performed in an anechoic chamber with a background noise of 16 dBA with a noise meter installed at a position of 0.3 m from the core surface using an A-weighted network.

[0182] With respect to noise, noise during operation of the motors of Test Nos. 1, 16, 21, 31, 33, 35, 37, 39, 41, 43, 45, 47, 49, 51, 53, 55, 57, 59, and 61 was used as references, and differences from references using the same kind of steels were evaluated.

[0183] The orientation strength of the core material of each core is shown in Tables 3-1 to 3-8 together with motor loss and noise (relative values). The orientation strength shown here is a measured value for a core material after stress relieving annealing when the core is formed and then subjected to the stress relieving annealing.

TABLE-US-00004 TABLE 3-1 Whether any Stress relieving Difference in total Orientation strength Material steel one of Si.sub.s/Si.sub.r > 1.0, annealing amount of Average of core material Test sheet Ti.sub.r/Ti.sub.s > 1.0, Nb.sub.r/ Temperature Time Si, Mn, sol. Al grain of rotor or stator No. Core No. Nb.sub.s > 1.0 is satisfied (° C.) (hr) (mass %) size (μm) A B C D E F																																														
1	Stator A1	Not satisfied	800	2	0.00	80	1	—	20	—	—	10	Rotor A1	800	2	80	—	1	—	20	1	—	2	Stator A1																						
Not satisfied	800	2	0.00	80	1	—	20	—	—	10	Rotor A1	—	—	15	—	16	—	16	4	—	3	Stator A1	Not satisfied	800	2	0.00	80	1	—	20	—	—	10	Rotor A2	—	—	70	—	14	—	17	4	—	4	Stator A2	Not

satisfied 800 2 0.00 85 1 — 21 — — 32 Rotor A1 — — 15 — 16 4 — 5 Stator A2 Not
satisfied 800 2 0.00 85 1 — 21 — — 32 Rotor A2 — — 70 — 14 — 17 4 — 6 Stator A1 Not
satisfied 800 2 0.00 80 1 1 20 1 10 Rotor A3 — — *2 — 4 — 16 16 — 7 Stator A2 Not satisfied
800 2 0.00 70 1 — 21 — — 22 Rotor A3 — — *2 — 4 — 16 16 — 8 Stator A1 Not satisfied —
— 0.00 15 16 — 16 — — 32 Rotor A1 800 2 80 — 1 — 21 1 — 9 Stator A2 Not satisfied — —
0.00 70 14 — 17 — — 30 Rotor A1 800 2 80 — 1 — 21 1 — 10 Stator A4 Not satisfied 800 2 0.00
81 1.2 — 23 — — 20 Rotor A4 — — 16 — 14 — 16 4 — 11 Stator A5 Not satisfied 800 2 0.00 83
1.1 — 14 — — 10 Rotor A5 — — 17 — 16 — 10 4 — 12 Stator A4 Not satisfied 800 2 0.00 81
1.2 — 23 1 1 20 Rotor A5 800 2 82 — 1.1 — 14 4 — 14 Stator A5 Not satisfied 800 2 0.00 82 1.1
— 14 — — 20 Rotor A4 800 2 81 — 1.2 — 23 4 — 15 Stator A6 Not satisfied 800 2 0.00 82 1 —
14 — — 10 Rotor A6 — — 72 — 16 — 10 4 — 16 Stator B1 Not satisfied 800 2 0.00 90 8 — 0.4
— — 2 Rotor B1 800 2 90 — 8 — 0.4 2 — *2 Texture is processed as it is cold rolled

TABLE-US-00005 TABLE 3-2 Whether any Stress relieving Difference in total Orientation
strength Material steel one of Si.sub.s/Si.sub.r > 1.0, annealing amount of Si, Average of core
material Test sheet Ti.sub.r/Ti.sub.s > 1.0, Nb.sub.r/ Temperature Time Mn, sol. Al grain of rotor or
stator No. Core No. Nb.sub.s > 1.0 is satisfied (° C.) (hr) (mass %) size (µm) A B C D E F 17 Stator
B2 Not satisfied 800 2 0.00 91 7 — 2 — — 2 Rotor B1 800 2 90 — 8 — 1 2 — 18 Stator B3 Not
satisfied 800 2 0.00 89 7 — 2 — — 2 Rotor B1 800 2 90 — 8 — 1 2 — 19 Stator B1 Satisfied 800
2 0.02 90 8 — 2 — — 2 Rotor C1 800 2 20 — 12 — 1 7 — 20 Stator B1 Satisfied 800 2 0.02 90 8
— 2 — — 2 Rotor C2 800 2 20 — 32 — 0.4 7 — 21 Stator D1 Not satisfied 800 2 0.00 81 1 — 17
— — 8 Rotor D1 800 2 81 — 1 — 17 3 — 22 Stator D1 Not satisfied 800 2 0.00 81 1 — 17 — —
8 Rotor D1 — — 21 — 12 — 12 5 — 23 Stator D2 Not satisfied 800 2 0.00 80 1 — 16 — — 8
Rotor D2 — — 70 — 12 — 11 7 — 24 Stator D1 Not satisfied 800 2 0.00 81 1 — 17 — — 8 Rotor
D3 — — *2 — 8 — 14 2 — 25 Stator D2 Not satisfied 800 2 0.00 80 1 1 16 — — 8 Rotor D3 —
— *2 — 8 — 14 2 — 26 Stator D1 Satisfied 800 2 0.01 81 1 — 17 — — 8 Rotor E1 — — 20 —
16 — 15 3 — 27 Stator D1 Satisfied 800 2 0.01 81 1 — 17 — — 8 Rotor E2 — — 20 — 32 — 0.4
3 — 28 Stator A1 Satisfied 800 2 3.87 80 1 — 20 — — 10 Rotor D1 — — 21 — 12 — 12 5 — 29
Stator A1 Satisfied 800 2 3.87 80 1 — 20 — — 10 Rotor V1 — — 21 — 12 — 12 5 — 30 Stator
A1 Satisfied 800 2 3.85 80 1 — 20 — — 10 Rotor W1 — — 21 — 12 — 12 5 — 31 Stator F1 Not
satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor F1 800 2 80 — 1 — 20 1 — *2 Texture is
processed as it is cold rolled

TABLE-US-00006 TABLE 3-3 Whether any Stress relieving Difference in total Orientation
strength Material steel one of Si.sub.s/Si.sub.r > 1.0, annealing amount of Si, Average of core
material Test sheet Ti.sub.r/Ti.sub.s > 1.0, Nb.sub.r/ Temperature Time Mn, sol. Al grain of rotor or
stator No. Core No. Nb.sub.s > 1.0 is satisfied (° C.) (hr) (mass %) size (µm) A B C D E F 32 Stator
F1 Not satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor F1 — — 71 — 15 — 16 5 — 33 Stator G1
Not satisfied 800 2 0.00 83 1 — 20 — — 10 Rotor G1 800 2 83 — 1 — 20 1 — 34 Stator G1 Not
satisfied 800 2 0.00 83 1 — 20 — — 10 Rotor G1 — — 69 — 15 — 16 5 — 35 Stator H1 Not
satisfied 800 2 0.00 82 1 — 20 — — 10 Rotor H1 800 2 82 — 1 — 20 1 — 36 Stator H1 Not
satisfied 800 2 0.00 82 1 — 20 — — 10 Rotor H1 — — 72 — 16 — 16 4 — 37 Stator I1 Not
satisfied 800 2 0.00 79 1 — 20 — — 10 Rotor I1 800 2 79 — 1 — 20 1 — 38 Stator I1 Not
satisfied 800 2 0.00 79 1 — 20 — — 10 Rotor I1 — — 68 — 16 — 16 4 — 39 Stator J1 Not
satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor J1 800 2 80 — 1 — 20 1 — 40 Stator J1 Not
satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor J1 — — 71 — 16 — 16 4 — 41 Stator K1 Not
satisfied 800 2 0.00 83 1 — 20 — — 10 Rotor K1 800 2 83 — 1 — 20 1 — 42 Stator K1 Not
satisfied 800 2 0.00 83 1 — 20 — — 10 Rotor K1 — — 70 — 16 — 16 4 — 43 Stator L1 Not
satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor L1 800 2 80 — 1 — 20 1 — 44 Stator L1 Not
satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor L1 — — 69 — 16 — 16 4 — 45 Stator M1 Not
satisfied 800 2 0.00 81 1 — 20 — — 10 Rotor M1 800 2 81 — 1 — 20 1 — 46 Stator M1 Not
satisfied 800 2 0.00 81 1 — 20 — — 10 Rotor M1 — — 72 — 16 — 16 4 —

TABLE-US-00007 TABLE 3-4 Whether any Stress relieving Difference in total Orientation strength Material steel one of Si.sub.s/Si.sub.r > 1.0, annealing amount of Si, Average of core material Test sheet Ti.sub.r/Ti.sub.s > 1.0, Nb.sub.r/ Temperature Time Mn, sol. Al grain of rotor or stator No. Core No. Nb.sub.s > 1.0 is satisfied (° C.) (hr) (mass %) size (μm) A B C D E F 47 Stator N1 Not satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor N1 800 2 80 — 1 — 20 1 — 48 Stator N1 Not satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor N1 — — 71 — 16 — 16 4 — 49 Stator 01 Not satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor 01 800 2 80 — 1 — 20 1 — 50 Stator 01 Not satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor 01 — — 72 — 16 — 16 4 — 51 Stator P Not satisfied 800 2 0.00 78 1 — 20 — — 10 Rotor P1 800 2 78 — 1 — 20 1 — 52 Stator P1 Not satisfied 800 2 0.00 78 1 — 20 — — 10 Rotor P1 — — 67 — 16 — 16 4 — 53 Stator Q1 Not satisfied 800 2 0.00 79 1 — 20 — — 10 Rotor Q1 800 2 79 — 1 — 20 1 — 54 Stator Q1 Not satisfied 800 2 0.00 79 1 — 20 — — 10 Rotor Q1 — — 70 — 16 — 16 4 — 55 Stator R1 Not satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor R1 800 2 80 — 1 — 20 1 — 56 Stator R1 Not satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor R1 — — 59 — 16 — 16 4 — 57 Stator S1 Not satisfied 800 2 0.00 81 1 — 20 — — 10 Rotor S1 800 2 81 — 1 — 20 1 — 58 Stator S1 Not satisfied 800 2 0.00 81 1 — 20 — — 10 Rotor S1 — — 68 — 16 — 16 4 — 59 Stator T1 Not satisfied 800 2 0.00 82 1 — 20 — — 10 Rotor T1 800 2 82 — 1 — 20 1 — 60 Stator T1 Not satisfied 800 2 0.00 82 1 — 20 — — 10 Rotor T1 — — 70 — 16 — 16 4 — 61 Stator U1 Not satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor U1 800 2 80 — 1 — 20 1 — 62 Stator U1 Not satisfied 800 2 0.00 80 1 — 20 — — 10 Rotor U1 — — 71 — 16 — 16 4 —

TABLE-US-00008 TABLE 3-5 Relational expression of orientation Relational expression of Test strength orientation strength No. B/A C/D B/E C/F B/A > 1.0 C/D > 1.0 B/E > 1.0 C/F > 1.0 1 1.0 1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied Satisfied 2 16.0 1.3 4.0 2.0 Satisfied Satisfied Satisfied Satisfied 3 14.0 1.2 3.5 2.0 Satisfied Satisfied Satisfied Satisfied 4 16.0 1.3 4.0 0.7 Satisfied Satisfied Satisfied Not satisfied 5 14.0 1.2 3.5 0.7 Satisfied Satisfied Satisfied Not satisfied 6 4.0 1.3 0.3 2.0 Satisfied Satisfied Not satisfied Satisfied 7 4.0 1.3 0.3 1.0 Satisfied Satisfied Not satisfied Not satisfied 8 0.1 0.8 1.0 0.5 Not satisfied Not satisfied Not satisfied Not satisfied 9 0.1 0.8 1.0 0.6 Not satisfied Not satisfied Not satisfied Not satisfied 10 11.7 1.4 3.5 1.2 Satisfied Satisfied Satisfied Satisfied 11 14.5 1.4 4.0 1.4 Satisfied Satisfied Satisfied Satisfied 12 0.9 1.6 0.3 1.2 Not satisfied Satisfied Not satisfied Satisfied 14 1.1 0.6 0.3 0.7 Satisfied Not satisfied Not satisfied Not satisfied 15 16.0 1.4 4.0 1.4 Satisfied Satisfied Satisfied Satisfied 16 1.0 1.0 4.0 0.2 Not satisfied Not satisfied Satisfied Not satisfied 17 1.1 2.0 4.0 1.0 Satisfied Satisfied Satisfied Not satisfied 18 1.1 2.0 4.0 1.0 Satisfied Satisfied Satisfied Not satisfied 19 1.5 2.0 1.7 1.0 Satisfied Satisfied Satisfied Not satisfied 20 4.0 5.0 4.6 1.0 Satisfied Satisfied Satisfied Not satisfied 21 1.0 1.0 0.3 2.1 Not satisfied Not satisfied Not satisfied Satisfied 22 12.0 1.4 2.4 2.1 Satisfied Satisfied Satisfied Satisfied 23 12.0 1.5 1.7 2.0 Satisfied Satisfied Satisfied Satisfied 24 8.0 1.2 4.0 2.1 Satisfied Satisfied Satisfied Satisfied 25 8.0 1.1 4.0 2.0 Satisfied Satisfied Satisfied Satisfied 26 16.0 1.1 5.3 2.1 Satisfied Satisfied Satisfied Satisfied 27 32.0 42.5 10.7 2.1 Satisfied Satisfied Satisfied Satisfied 28 12.0 1.7 2.4 2.0 Satisfied Satisfied Satisfied Satisfied 29 12.0 1.7 2.4 2.0 Satisfied Satisfied Satisfied Satisfied 30 12.0 1.7 2.4 2.0 Satisfied Satisfied Satisfied Satisfied 31 1.0 1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied Satisfied 32 15.0 1.3 3.0 2.0 Satisfied Satisfied Satisfied Satisfied

TABLE-US-00009 TABLE 3-6 Relational expression of orientation Relational expression of Test strength orientation strength No. B/A C/D B/E C/F B/A>1.0 C/D>1.0 B/E>1.0 C/F>1.0 33 1.0 1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied Satisfied 34 15.0 1.3 3.0 2.0 Satisfied Satisfied Satisfied Satisfied 35 1.0 1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied Satisfied 36 16.0 1.3 4.0 2.0 Satisfied Satisfied Satisfied Satisfied 37 1.0 1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied Satisfied 38 16.0 1.3 4.0 2.0 Satisfied Satisfied Satisfied Satisfied 39 1.0 1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied Satisfied 40 16.0 1.3 4.0 2.0 Satisfied Satisfied Satisfied Satisfied 41 1.0 1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied Satisfied 42 16.0 1.3 4.0 2.0

Satisfied Satisfied Satisfied Satisfied 43 1.0 1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied
Satisfied 44 16.0 1.3 4.0 2.0 Satisfied Satisfied Satisfied Satisfied 45 1.0 1.0 1.0 2.0 Not satisfied
Not satisfied Not satisfied Satisfied 46 16.0 1.3 4.0 2.0 Satisfied Satisfied Satisfied Satisfied 47 1.0
1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied Satisfied 48 16.0 1.3 4.0 2.0 Satisfied Satisfied
Satisfied Satisfied 49 1.0 1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied Satisfied 50 16.0 1.3
4.0 2.0 Satisfied Satisfied Satisfied Satisfied 51 1.0 1.0 1.0 2.0 Not satisfied Not satisfied Not
satisfied Satisfied 52 16.0 1.3 4.0 2.0 Satisfied Satisfied Satisfied Satisfied 53 1.0 1.0 1.0 2.0 Not
satisfied Not satisfied Not satisfied Satisfied 54 16.0 1.3 4.0 2.0 Satisfied Satisfied Satisfied
Satisfied 55 1.0 1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied Satisfied 56 16.0 1.3 4.0 2.0
Satisfied Satisfied Satisfied Satisfied 57 1.0 1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied
Satisfied 58 16.0 1.3 4.0 2.0 Satisfied Satisfied Satisfied Satisfied 59 1.0 1.0 1.0 2.0 Not satisfied
Not satisfied Not satisfied Satisfied 60 16.0 1.3 4.0 2.0 Satisfied Satisfied Satisfied Satisfied 61 1.0
1.0 1.0 2.0 Not satisfied Not satisfied Not satisfied Satisfied 62 16.0 1.3 4.0 2.0 Satisfied Satisfied
Satisfied Satisfied

TABLE-US-00010 TABLE 3-7 Test No. Motor loss (W) Noise (dB) Determination 1 45 Reference
A Comparative Example 2 42 -3 Invention Example 3 42 -3 Invention Example 4 43 -3 Invention
Example 5 43 -3 Invention Example 6 43 -2 Invention Example 7 43 -2 Invention Example 8 49
+2 Comparative Example 9 49 +2 Comparative Example 10 42 -3 Invention Example 11 40 -3
Invention Example 12 49 +2 Comparative Example 14 49 +2 Comparative Example 15 42 -3
Invention Example 16 50 Reference B Comparative Example 17 49 -3 Invention Example 18 49
-3 Invention Example 19 49 -5 Invention Example 20 60 +2 Comparative Example 21 61
Reference D Comparative Example 22 59 -3 Invention Example 23 59 -3 Invention Example 24
60 -2 Invention Example 25 60 -2 Invention Example 26 60 -2 Invention Example 27 71 +2
Comparative Example 28 44 -3 Invention Example 29 44 -3 Invention Example 30 44 -3
Invention Example 31 45 Reference F Comparative Example 32 42 -3 Invention Example

TABLE-US-00011 TABLE 3-8 Test No. Motor loss (W) Noise (dB) Determination 33 45
Reference G Comparative Example 34 42 -3 Invention Example 35 44 Reference H Comparative
Example 36 40 -3 Invention Example 37 43 Reference I Comparative Example 38 41 -3 Invention
Example 39 44 Reference J Comparative Example 40 42 -2 Invention Example 41 45 Reference K
Comparative Example 42 40 -3 Invention Example 43 43 Reference L Comparative Example 44
42 -3 Invention Example 45 43 Reference M Comparative Example 46 42 -2 Invention Example
47 44 Reference N Comparative Example 48 41 -2 Invention Example 49 43 Reference O
Comparative Example 50 40 -3 Invention Example 51 44 Reference P Comparative Example 52
42 -3 Invention Example 53 45 Reference Q Comparative Example 54 42 -3 Invention Example
55 44 Reference R Comparative Example 56 42 -2 Invention Example 57 43 Reference S
Comparative Example 58 41 -2 Invention Example 59 45 Reference T Comparative Example 60
42 -3 Invention Example 61 44 Reference U Comparative Example 62 40 -3 Invention Example

[0184] The effect of the present invention is evaluated by a relative value with respect to motor loss
and noise in a motor in which the core material of the stator and the core material of the rotor are
made of the same steel sheet. In the motor in which the core material of the stator and the core
material of the rotor are made of different steel sheets, a case where motor loss and noise are
smaller than those of the motor made of the same steel sheet (steel sheets having the same kind of
steel and manufacturing conditions) is an invention example.

[0185] Test Nos. 1, 16, 21, 31, 33, 35, 37, 39, 41, 43, 45, 47, 49, 51, 53, 55, 57, 59, and 61 in
Tables 3-1 to 3-8 are examples in which the core materials of the stator and the rotor are of the
same kind of steel and steel sheets having the same stress relieving annealing conditions are used,
and these are defined as Comparative Example (Reference A), Comparative Example (Reference
B), Comparative Example (Reference D), Comparative Example (Reference F), Comparative
Example (Reference G), Comparative Example (Reference H), Comparative Example (Reference
I), Comparative Example (Reference J), Comparative Example (Reference K), Comparative

Example (Reference L), Comparative Example (Reference M), Comparative Example (Reference N), Comparative Example (Reference O), Comparative Example (Reference P), Comparative Example (Reference Q), Comparative Example (Reference R), Comparative Example (Reference S), Comparative Example (Reference T), and Comparative Example (Reference U), respectively. [0186] Test Nos. 1 to 15 are examples using steel type A described in Table 1. It can be seen that the motor loss and noise of Nos. 2 to 7, 10, 11, and 15 as invention examples are both lower than those of Comparative Example (Reference A) as a reference.

[0187] Test Nos. 16 to 18 are examples using component B described in Table 1. No. 17 as an invention example and No. 18 as an invention example are examples in which the $\{111\} \langle 211 \rangle$ orientation strength of the core material of the stator is weakened and the $\{411\} \langle 011 \rangle$ orientation strength is increased by change in the cold rolling reduction in No. 17 and change in the temperature rising rate in No. 18.

[0188] Also, Test No. 19 is an example in which a steel sheet in which the $\{111\} \langle 211 \rangle$ orientation strength is increased by containing Nb is applied as the core material of the rotor.

[0189] It can be seen that the motor loss and noise of Invention Examples 17 to 19 are both lower than those of Test No. 16 (Comparative Example (Reference B)) as a reference.

[0190] Test Nos. 21 to 25 are examples using component D described in Table 1. It can be seen that the motor loss and noise of Nos. 22 to 25 as invention examples are both lower than those of Test No. 21 (Comparative Example (Reference D)) as a reference.

[0191] In Test No. 26, a steel sheet material is a combination of a stator (D1) and a rotor (E1). A steel sheet in which the $\{111\} \langle 211 \rangle$ orientation strength is increased by containing Ti is applied as the core material of the rotor, and the motor loss and noise are both lower than those in Test No. 21 (Comparative Example (Reference D)).

[0192] Invention Examples Nos. 28, 29, and 30 are combinations of a rotor (D1), a rotor (V1), or a rotor (W1) with respect to a stator (A1). In these examples, a transformational material (low Si steel) is applied to the core material of the rotor to increase the $\{111\} \langle 211 \rangle$ orientation strength, and the motor loss and noise are both lower than those in Test No. 21 (Comparative Example (Reference D)).

[0193] Test Nos. 31 to 32 are examples using steel type F described in Table 1. It can be seen that the motor loss and noise of Test No. 32 as an invention example are both lower than those of Test No. 31 (Comparative Example (Reference F)) as a reference.

[0194] Test Nos. 33 to 34 are examples using steel type G described in Table 1. It can be seen that the motor loss and noise of Test No. 34 as an invention example are both lower than those of No. 33 (Comparative Example (Reference G)) as a reference.

[0195] Similarly, Test Nos. 36 to 62 are examples using steel types H to U described in Table 1.

[0196] It can be seen that the motor loss and noise of Test Nos. 36, 38, 40, 42, 44, 46, 48, 50, 52, 54, 56, 58, 60, and 62 are both lower than those of Test Nos. 35, 37, 39, 41, 43, 45, 47, 49, 51, 53, 55, 57, 59, and 61, which are references using similar kind of steels, respectively.

[0197] On the other hand, in Test Nos. 8, 9, 12, 14, 20, and 27, the predetermined orientation strength was not obtained, and the motor loss and the noise were inferior to the references.

[0198] The rotary electric machine according to the present invention has excellent characteristics in motor loss and noise by applying different steel sheets having appropriately controlled chemical composition, hot rolling conditions, cold rolling conditions, and annealing conditions, respectively, as the core material of the stator and the core material of the rotor.

Field of Industrial Application

[0199] According to the present invention, it is possible to provide a rotary electric machine excellent in motor loss and noise, and thus it is industrially extremely useful.

BRIEF DESCRIPTION OF THE REFERENCE SYMBOLS

[0200] **3** Stator core [0201] **300** Motor [0202] **301** Housing [0203] **302** Rotor

Claims

1. A rotary electric machine comprising: a stator; a rotor; and a housing that houses the stator and the rotor, wherein A which is an $\{111\} \langle 211 \rangle$ orientation strength of a base steel sheet of a non-oriented electrical steel sheet included in the stator is less than 15, B which is an $\{111\} \langle 211 \rangle$ orientation strength of a base steel sheet of a non-oriented electrical steel sheet included in the rotor is 2 to 30, and the A and the B satisfy a relationship of $B/A > 1.0$, C which is an $\{411\} \langle 011 \rangle$ orientation strength of the base steel sheet of the non-oriented electrical steel sheet included in the stator is 2 to 50, D which is an $\{411\} \langle 011 \rangle$ orientation strength of the base steel sheet of the non-oriented electrical steel sheet included in the rotor is 1 to 40, and the C and the D satisfy a relationship of $C/D > 1.0$, and the base steel sheets of the non-oriented electrical steel sheet included in the rotor and the non-oriented electrical steel sheet included in the stator each having a chemical composition including, in mass %, C: 0.0100% or less, Si: 0.5000 to 4.0000%, sol.Al: 0.0001 to 1.0000%, S: 0.0100% or less, N: 0.0100% or less, one or more of Mn, Ni, Co, Pt, Pb, Cu, and Au: 0.1000 to 5.0000% in total, Cr: 0 to 2.0000%, Sn: 0 to 0.4000%, Sb: 0 to 0.4000%, P: 0 to 0.4000%, Ti: 0 to 0.1000%, Nb: 0 to 0.1000%, Zr: 0 to 0.1000%, V: 0 to 0.1000%, and the remainder comprising Fe and impurities.
2. The rotary electric machine according to claim 1, wherein in the non-oriented electrical steel sheet included in the rotor, the B and E which is an $\{111\} \langle 011 \rangle$ orientation strength satisfy a relationship of $B/E > 1.0$.
3. The rotary electric machine according to claim 1, wherein in the non-oriented electrical steel sheet included in the stator, the C and F which is an $\{100\} \langle 011 \rangle$ orientation strength satisfy a relationship of $C/F > 1.0$.
4. The rotary electric machine according to claim 1, wherein difference in a total of the Si content, the Mn content, and the sol.Al content in the base steel sheets between the non-oriented electrical steel sheet included in the stator and the non-oriented electrical steel sheet included in the rotor is within 0.20 mass %, and an average grain size of the non-oriented electrical steel sheet included in the stator is larger than an average grain size of the non-oriented electrical steel sheet included in the rotor.
5. The rotary electric machine according to claim 1, wherein when the Si content, the Ti content, and the Nb content in mass % of the base steel sheet of the non-oriented electrical steel sheet included in the stator are respectively denoted by Si.sub.s, Ti.sub.s, and Nb.sub.s, and the Si content, the Ti content, and the Nb content of the base steel sheet of the non-oriented electrical steel sheet included in the rotor are respectively denoted by Si.sub.r, Ti.sub.r, and Nb.sub.r, any one of $Si.sub.s/Si.sub.r > 1.0$, $Ti.sub.r/Ti.sub.s > 1.0$, and $Nb.sub.r/Nb.sub.s > 1.0$ is satisfied.
6. The rotary electric machine according to claim 1, wherein when the Nb content, the Zr content, the Ti content, the V content, the C content, and the N content in mass % of the base steel sheet of the non-oriented electrical steel sheet included in the stator are respectively denoted by Nb.sub.s, Zr.sub.s, Ti.sub.s, V.sub.s, C.sub.s, and N.sub.s,
 $0 \geq Nb.sub.s/93 + Zr.sub.s/91 + Ti.sub.s/48 + V.sub.s/51 - (C.sub.s/12 + N.sub.s/14)$ is satisfied.
7. The rotary electric machine according to claim 1, wherein when the Nb content, the Zr content, the Ti content, the V content, the C content, and the N content in mass % of the base steel sheet of the non-oriented electrical steel sheet included in the rotor are respectively denoted by Nb.sub.r, Zr.sub.r, Ti.sub.r, V.sub.r, C.sub.r, and N.sub.r, $0 < Nb.sub.r/93 + Zr.sub.r/91 + Ti.sub.r/48 + V.sub.r/51 - (C.sub.r/12 + N.sub.r/14) < 5.0 \times 10^{-3}$ is satisfied.
8. A non-oriented electrical steel sheet comprising: a base steel sheet; and an insulating coating formed on a surface of the base steel sheet, the base steel sheet having a chemical composition including, in mass %, C: 0.0100% or less, Si: 0.5000 to 4.0000%, sol.Al: 0.0001 to 1.0000%, S: 0.0100% or less, N: 0.0100% or less, one or more of Mn, Ni, Co, Pt, Pb, Cu, and Au: 0.1000 to

5.0000% in total, Cr: 0 to 2.0000%, Sn: 0 to 0.4000%, Sb: 0 to 0.4000%, P: 0 to 0.4000%, Ti: 0 to 0.1000%, Nb: 0 to 0.1000%, Zr: 0 to 0.1000%, V: 0 to 0.1000%, and the remainder comprising Fe and impurities, and in the base steel sheet, an {111} <211> orientation strength being less than 15, and an {411} <011> orientation strength being 2 to 50.

9. A non-oriented electrical steel sheet comprising: a base steel sheet; and an insulating coating formed on a surface of the base steel sheet, the base steel sheet having a chemical composition including, in mass %, C: 0.0100% or less, Si: 0.5000 to 4.0000%, sol.Al: 0.0001 to 1.0000%, S: 0.0100% or less, N: 0.0100% or less, one or more of Mn, Ni, Co, Pt, Pb, Cu, and Au: 0.1000 to 5.0000% in total, Cr: 0 to 2.0000%, Sn: 0 to 0.4000%, Sb: 0 to 0.4000%, P: 0 to 0.4000%, Ti: 0 to 0.1000%, Nb: 0 to 0.1000%, Zr: 0 to 0.1000%, V: 0 to 0.1000%, and the remainder comprising Fe and impurities, and in the base steel sheet, an {111} <211> orientation strength being 2 to 30, and an {411} <011> orientation strength being 1 to 40.

10. A laminated core, wherein the non-oriented electrical steel sheets according to claim **8** are laminated.

11. A laminated core, wherein the non-oriented electrical steel sheets according to claim **9** are laminated.

12. The rotary electric machine according to claim 1, wherein the non-oriented electrical steel sheet included in the stator is a steel sheet obtained by further performing heat treatment at 600° C. or higher on the non-oriented electrical steel sheet included in the rotor.

13. A method for manufacturing a laminated core, comprising: a step of processing and laminating the non-oriented electrical steel sheets according to claim 8.

14. A method for manufacturing a laminated core, comprising: a step of processing and laminating the non-oriented electrical steel sheets according to claim 9.

15. A method for manufacturing a rotary electric machine, comprising: a step of assembling a laminated core comprising a laminated non-oriented electrical steel sheet comprising: a base steel sheet; and an insulating coating formed on a surface of the base steel sheet, the base steel sheet having a chemical composition including, in mass %, C: 0.0100% or less, Si: 0.5000 to 4.0000%, sol.Al: 0.0001 to 1.0000%, S: 0.0100% or less, N: 0.0100% or less, one or more of Mn, Ni, Co, Pt, Pb, Cu, and Au: 0.1000 to 5.0000% in total, Cr: 0 to 2.0000%, Sn: 0 to 0.4000%, Sb: 0 to 0.4000%, P: 0 to 0.4000%, Ti: 0 to 0.1000%, Nb: 0 to 0.1000%, Zr: 0 to 0.1000%, V: 0 to 0.1000%, and the remainder comprising Fe and impurities, and in the base steel sheet, an {111} <211> orientation strength being less than 15, and an {411} <011> orientation strength being 2 to 50, and the laminated core according to claim 11.

16. The rotary electric machine according to claim 2, wherein difference in a total of the Si content, the Mn content, and the sol.Al content in the base steel sheets between the non-oriented electrical steel sheet included in the stator and the non-oriented electrical steel sheet included in the rotor is within 0.20 mass %, and an average grain size of the non-oriented electrical steel sheet included in the stator is larger than an average grain size of the non-oriented electrical steel sheet included in the rotor.

17. The rotary electric machine according to claim 3, wherein difference in a total of the Si content, the Mn content, and the sol.Al content in the base steel sheets between the non-oriented electrical steel sheet included in the stator and the non-oriented electrical steel sheet included in the rotor is within 0.20 mass %, and an average grain size of the non-oriented electrical steel sheet included in the stator is larger than an average grain size of the non-oriented electrical steel sheet included in the rotor.

18. The rotary electric machine according to claim 2, wherein when the Si content, the Ti content, and the Nb content in mass % of the base steel sheet of the non-oriented electrical steel sheet included in the stator are respectively denoted by Si.sub.s, Ti.sub.s, and Nb.sub.s, and the Si content, the Ti content, and the Nb content of the base steel sheet of the non-oriented electrical steel sheet included in the rotor are respectively denoted by Si.sub.r, Ti.sub.r, and Nb.sub.r, any one of

$\text{Si.sub.s}/\text{Si.sub.r}>1.0$, $\text{Ti.sub.r}/\text{Ti.sub.s}>1.0$, and $\text{Nb.sub.r}/\text{Nb.sub.s}>1.0$ is satisfied.

19. The rotary electric machine according to claim 3, wherein when the Si content, the Ti content, and the Nb content in mass % of the base steel sheet of the non-oriented electrical steel sheet included in the stator are respectively denoted by Si.sub.s , Ti.sub.s , and Nb.sub.s , and the Si content, the Ti content, and the Nb content of the base steel sheet of the non-oriented electrical steel sheet included in the rotor are respectively denoted by Si.sub.r , Ti.sub.r , and Nb.sub.r , any one of $\text{Si.sub.s}/\text{Si.sub.r}>1.0$, $\text{Ti.sub.r}/\text{Ti.sub.s}>1.0$, and $\text{Nb.sub.r}/\text{Nb.sub.s}>1.0$ is satisfied.

20. The rotary electric machine according to claim 2, wherein when the Nb content, the Zr content, the Ti content, the V content, the C content, and the N content in mass % of the base steel sheet of the non-oriented electrical steel sheet included in the stator are respectively denoted by Nb.sub.s , Zr.sub.s , Ti.sub.s , V.sub.s , C.sub.s , and N.sub.s ,

$0 \geq \text{Nb.sub.s}/93 + \text{Zr.sub.s}/91 + \text{Ti.sub.s}/48 + \text{V.sub.s}/51 - (\text{C.sub.s}/12 + \text{N.sub.s}/14)$ is satisfied.
