



US 20250287834A1

(19) **United States**(12) **Patent Application Publication****Kwon et al.**(10) **Pub. No.: US 2025/0287834 A1**(43) **Pub. Date: Sep. 11, 2025**(54) **BORON COMPOUND AND ORGANIC
LIGHT-EMITTING DEVICE COMPRISING
SAME**(71) Applicant: **University-Industry Cooperation
Group of Kyung Hee University,
Yongin-si (KR)**(72) Inventors: **Jang Hyuk Kwon**, Seongnam-si (KR);
Braveenth Ramanaskanda, Seoul
(KR); **Ju Young Lee**, Suwon-si (KR);
Jae Doh Park, Seoul (KR); **Hyun A
Lee**, Seoul (KR); **Hye In Yang**, Seoul
(KR)(21) Appl. No.: **18/687,228**(22) PCT Filed: **Aug. 2, 2022**(86) PCT No.: **PCT/KR2022/011432**

§ 371 (c)(1),


(2) Date: **Feb. 27, 2024**(30) **Foreign Application Priority Data**

Sep. 1, 2021 (KR) 10-2021-0116437


Publication Classification(51) **Int. Cl.**
H10K 85/60 (2023.01)
C07F 5/02 (2006.01)**C07F 7/08** (2006.01)**C09K 11/02** (2006.01)**C09K 11/06** (2006.01)**H10K 50/12** (2023.01)**H10K 101/00** (2023.01)(52) **U.S. Cl.**CPC **H10K 85/636** (2023.02); **C07F 5/027**
(2013.01); **C07F 7/0812** (2013.01); **C09K**
11/02 (2013.01); **C09K 11/06** (2013.01); **H10K**
85/615 (2023.02); **H10K 85/6574** (2023.02);
C07B 2200/05 (2013.01); **C09K 2211/1007**
(2013.01); **C09K 2211/1014** (2013.01); **C09K**
2211/1022 (2013.01); **H10K 50/12** (2023.02);
H10K 85/658 (2023.02); **H10K 2101/27**
(2023.02)(57) **ABSTRACT**

The present invention relates to: a boron compound having a structure comprising a specific substituent; and an organic light-emitting device comprising same, and more specifically, to a boron compound having improved quantum efficiency and lifespan characteristics by, while attaching a substituent capable of disrupting intermolecular packing at the para position of boron, which does not significantly affect color characteristics, transforming the boron core inner structure, which affects color characteristics, into a carbazole form having only one side substituted with a heteroatom aromatic ring, and an organic light-emitting device comprising the same.


【FIG. 1a】




【FIG. 1b】




【FIG. 2a】




【FIG. 2b】




【FIG. 3a】




【FIG. 3b】



【FIG. 4a】



【FIG. 4b】



BORON COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE COMPRISING SAME

CROSS-REFERENCE TO RELATED APPLICATION

[0001] This Application is a Section 371 National Stage Application of International Application No. PCT/KR2022/011432, filed Aug. 2, 2022 and published as WO 2023/033381 A1, in Korean, which claims priority to KR patent application serial no. 10-2021-0116437, filed Sep. 1, 2021, the contents of which are hereby incorporated by reference in their entirety.

TECHNICAL FIELD

[0002] The present invention relates to a boron delayed fluorescent compound (thermally activated delayed fluorescence) having narrow half-width characteristics and an organic light-emitting device having improved color characteristics by using the same.

BACKGROUND ART

[0003] Organic light emission refers to a phenomenon of converting electrical energy to light energy using organic materials. Herein, an organic light-emitting device is a device having the organic materials formed in multiple layers between an anode and a cathode, and emitting light when electrical energy is applied. An organic light-emitting device is formed with multiple organic layers for efficiency and stability, and may basically be formed with a hole injection layer, a hole transport layer, a light-emitting layer, an electron transport layer, an electron injection layer and the like.

[0004] Materials used as the organic layers may be divided into light-emitting materials and charge transport materials depending on the function, and the light-emitting materials may be classified into fluorescent materials using only fluorescence derived from a singlet excited state of electrons and phosphorescent materials derived from a triplet excited state depending on the light-emitting mechanism. In addition, the light-emitting materials may be divided into blue, green and red light-emitting materials depending on the light-emitting color, and phosphorescent materials are used in industry for all colors other than blue.

[0005] As for the blue light-emitting material, only fluorescent materials with reduced efficiency by using only singlet are used due to limitations in lifespan and color characteristics. Accordingly, as the blue light-emitting material, phosphorescent materials using triplet by using heavy metals such as iridium or platinum and delayed fluorescent materials using triplet with only pure organic materials by reducing an energy difference between singlet and triplet are being developed.

[0006] However, although high efficiency may be achieved when using the phosphorescent material, the price of heavy metals used for obtaining phosphorescence is high, and various social problems may be caused during mining.


[0007] Unlike existing fluorescence using only singlet energy and thereby having a triplet energy loss corresponding to 75%, delayed fluorescence induces a reverse intersystem crossing (RISC) phenomenon from triplet to singlet using only room temperature heat energy by designing molecules so that an energy difference between singlet and

triplet is reduced, and as a result, energy of both triplet and singlet may be utilized. Accordingly, triplet may be used without heavy metal materials as with a phosphorescent material, resulting in higher light emission efficiency of a material compared to a fluorescent material, and it is called delayed fluorescence since fluorescence emission is obtained via triplet.

[0008] Characteristics of an organic light-emitting device may depend on a dopant material of a light-emitting layer, and a delayed fluorescent dopant needs to have a small overlap between HOMO (Highest Occupied Molecular Orbital) and LUMO (Lowest Unoccupied Molecular Orbital) in order to minimize the energy difference between singlet and triplet. For this purpose, a donor-acceptor structure is mostly used, and the structure has a characteristic of allowing intra charge transfer. However, when an existing compound having a donor-acceptor structure is used as a delayed fluorescent material, the emission wavelength shifts to a long wavelength region, and there is a disadvantage that color purity is inferior due to the wide luminescence spectrum.

[0009] In order to overcome this disadvantage, 'DABNA-1', an existing delayed fluorescent material having a multi-resonance effect (MR-TADF), was reported. The 'DABNA-1' has a structure of the following Chemical Formula a.

[Chemical Formula a]



[0010] While an existing delayed fluorescent material having a donor-acceptor structure reduces an overlap between HOMO and LUMO by a donor monomer unit, MR-TADF separates the overlap between HOMO and LUMO by a solid intramolecular atomic unit, and in addition, there is almost no molecular distortion when the molecule is excited by light, electricity or the like, allowing to have narrow half-width characteristics. However, in the DABNA-1 structure, intermolecular packing readily occurs due to the flat molecular structure in which the ring structures are tightly bound, and there is a disadvantage of worsened color characteristics caused by a shift to a longer wavelength or widened half-width characteristics in a thin film state compared to in a solution state. For example, DABNA-1 shows narrow half-width characteristics of 21 nm in a solution state, however, when doped to an actual mCBP host by 1 wt %, there is a problem of the half-width increasing to 27 nm.

DISCLOSURE


Technical Problem

[0011] In view of the above, the present invention is directed to providing a boron compound having excellent quantum efficiency, and having improved color characteristics in a thin film state.

[0012] The present invention is also directed to providing an organic light-emitting device having improved color characteristics and lifespan characteristics.

Technical Solution

[0013] In view of the above, a boron compound according to one embodiment of the present invention is represented by the following Chemical Formula 1.




[0014] In Chemical Formula 1,


[0015] X_1 to X_7 are each independently hydrogen, deuterium, a nitrile group, a halogen group, a substituted or unsubstituted $C_1\sim C_{10}$ alkyl group, a substituted or unsubstituted $C_3\sim C_{10}$ cycloalkyl group, a substituted or unsubstituted $C_1\sim C_{10}$ alkoxy group, a substituted or unsubstituted $C_1\sim C_{10}$ silyl group, a substituted or unsubstituted amine group, a substituted or unsubstituted $C_6\sim C_{20}$ aryl group, a substituted or unsubstituted $C_2\sim C_{20}$ heteroaryl group, a substituted or unsubstituted $C_{12}\sim C_{20}$ diarylamino group, a substituted or unsubstituted $C_4\sim C_{20}$ diheteroaryl amino group, or a substituted or unsubstituted $C_2\sim C_{20}$ arylheteroaryl amino group, Y_1 is N- R_4 , oxygen or sulfur, R_1 to R_3 are each independently hydrogen, deuterium, a nitrile group, a halogen group, a substituted or unsubstituted $C_1\sim C_{10}$ alkyl group, a substituted or unsubstituted $C_3\sim C_{10}$ cycloalkyl group, a substituted or unsubstituted $C_1\sim C_{10}$ alkoxy group, a substituted or unsubstituted $C_1\sim C_{10}$ silyl group, a substituted or unsubstituted amine group, a substituted or unsubstituted $C_6\sim C_{20}$ aryl group, a substituted or unsubstituted $C_2\sim C_{20}$ heteroaryl group, a substituted or unsubstituted $C_{12}\sim C_{20}$ diarylamino group, a substituted or unsubstituted $C_4\sim C_{20}$ diheteroaryl amino group, or a substituted or unsubstituted $C_2\sim C_{20}$ arylheteroaryl amino group, and R_4 is hydrogen, deuterium, a substituted or unsubstituted $C_1\sim C_{60}$ alkyl group, a substituted or unsubstituted $C_3\sim C_{10}$ cycloalkyl group, a substituted or unsubstituted $C_6\sim C_{60}$ aryl group, or a substituted or unsubstituted $C_6\sim C_{60}$ heteroaryl group.

[0016] The boron compound may specifically be represented by one of the following Chemical Formulae 2 to 126.


[Chemical Formulae 2]




[Chemical Formulae 3]



[Chemical Formulae 4]




[Chemical Formulae 5]




-continued


[Chemical Formulae 6]




[Chemical Formulae 7]



[Chemical Formulae 8]




[Chemical Formulae 9]




-continued


[Chemical Formulae 10]



[Chemical Formulae 11]




[Chemical Formulae 12]




-continued

[Chemical Formulae 13]




-continued


[Chemical Formulae 16]




[Chemical Formulae 14]




[Chemical Formulae 17]



[Chemical Formulae 15]




[Chemical Formulae 18]




-continued

[Chemical Formulae 19]




-continued

[Chemical Formulae 22]




[Chemical Formulae 23]

[Chemical Formulae 20]




[Chemical Formulae 24]

[Chemical Formulae 21]




[Chemical Formulae 25]




-continued

[Chemical Formulae 26]




-continued


[Chemical Formulae 29]




[Chemical Formulae 27]




[Chemical Formulae 30]



[Chemical Formulae 28]




[Chemical Formulae 31]




-continued

[Chemical Formulae 32]




-continued


[Chemical Formulae 35]




[Chemical Formulae 33]




[Chemical Formulae 36]



[Chemical Formulae 34]




[Chemical Formulae 37]




-continued

[Chemical Formulae 38]




-continued


[Chemical Formulae 41]




[Chemical Formulae 39]




[Chemical Formulae 42]



[Chemical Formulae 40]




[Chemical Formulae 43]




-continued


[Chemical Formulae 44]




[Chemical Formulae 45]



[Chemical Formulae 46]




[Chemical Formulae 47]




-continued


[Chemical Formulae 48]



[Chemical Formulae 49]




[Chemical Formulae 50]




-continued


[Chemical Formulae 51]



[Chemical Formulae 52]




[Chemical Formulae 53]




-continued


[Chemical Formulae 54]



[Chemical Formulae 55]




[Chemical Formulae 56]




-continued

[Chemical Formulae 57]




-continued

[Chemical Formulae 61]




[Chemical Formulae 62]



[Chemical Formulae 58]




[Chemical Formulae 59]




[Chemical Formulae 60]



[Chemical Formulae 63]




[Chemical Formulae 64]




-continued


[Chemical Formulae 65]




[Chemical Formulae 66]



[Chemical Formulae 67]




[Chemical Formulae 68]




-continued


[Chemical Formulae 69]




[Chemical Formulae 70]



[Chemical Formulae 71]




[Chemical Formulae 72]




-continued

[Chemical Formulae 73]




-continued


[Chemical Formulae 76]




[Chemical Formulae 77]




[Chemical Formulae 74]



[Chemical Formulae 78]




[Chemical Formulae 75]




-continued

[Chemical Formulae 79]




-continued


[Chemical Formulae 82]




[Chemical Formulae 80]




[Chemical Formulae 83]



[Chemical Formulae 81]




[Chemical Formulae 84]




-continued

[Chemical Formulae 85]





-continued

[Chemical Formulae 89]




[Chemical Formulae 90]

[Chemical Formulae 86]




[Chemical Formulae 91]



[Chemical Formulae 87]



[Chemical Formulae 88]




[Chemical Formulae 92]




-continued

[Chemical Formulae 93]




-continued


[Chemical Formulae 96]




[Chemical Formulae 94]




[Chemical Formulae 97]




[Chemical Formulae 98]



[Chemical Formulae 99]




[Chemical Formulae 95]




-continued


[Chemical Formulae 100]




[Chemical Formulae 101]



[Chemical Formulae 102]




[Chemical Formulae 103]




-continued


[Chemical Formulae 104]




[Chemical Formulae 105]



[Chemical Formulae 106]




[Chemical Formulae 107]




-continued


[Chemical Formulae 108]



[Chemical Formulae 109]




[Chemical Formulae 110]




-continued


[Chemical Formulae 111]




[Chemical Formulae 112]



[Chemical Formulae 113]




[Chemical Formulae 114]




-continued

[Chemical Formulae 115]




-continued


[Chemical Formulae 118]




[Chemical Formulae 116]




[Chemical Formulae 119]



[Chemical Formulae 117]




[Chemical Formulae 120]




-continued

[Chemical Formulae 121]




-continued


[Chemical Formulae 124]



[Chemical Formulae 122]





[Chemical Formulae 125]



[Chemical Formulae 126]

[Chemical Formulae 123]




[0017] An organic light-emitting device according to another embodiment of the present invention includes a first

electrode, a second electrode provided opposite to the first electrode, and an organic material layer located between the first electrode and the second electrode, wherein the organic material layer includes the boron compound.

[0018] The organic material layer may include an electron injection layer (EIL), an electron transport layer (ETL), a light-emitting layer (EML), a hole transport layer (HTL) and a hole injection layer (HIL).

[0019] The light-emitting layer may include an anthracene derivative represented by the following Chemical Formula 127 as a host compound.



[0020] In Chemical Formula 127, R_5 to R_{14} are each independently hydrogen, deuterium, a nitrile group, a halogen group, a substituted or unsubstituted $C_1\sim C_{10}$ alkyl group, a substituted or unsubstituted $C_3\sim C_{10}$ cycloalkyl group, a substituted or unsubstituted $C_1\sim C_{10}$ alkoxy group, a substituted or unsubstituted $C_1\sim C_{10}$ silyl group, a substituted or unsubstituted amine group, a substituted or unsubstituted $C_6\sim C_{20}$ aryl group, a substituted or unsubstituted $C_2\sim C_{20}$ heteroaryl group, a substituted or unsubstituted $C_{12}\sim C_{20}$ diarylamino group, a substituted or unsubstituted $C_4\sim C_{20}$ diheteroarylamino group, or a substituted or unsubstituted $C_2\sim C_{20}$ arylheteroarylamino group, L_1 and L_2 are each independently a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group, and k s are each independently an integer of 1 to 3.

[0021] In addition, the light-emitting layer includes a host compound, a first dopant compound and a second dopant compound, and the second dopant compound is a delayed fluorescent material or a phosphorescent material, and the first dopant compound may include the boron compound.

[0022] The delayed fluorescent material of the second dopant compound is a material having an electron donating-electron accepting structure, and the material having an electron donating-electron accepting structure may use one or more of a boron compound, a triazine, a cyano group and a sulfone group as the electron acceptor and one or more of a carbazole derivative and an acridane derivative as the electron donor, and the phosphorescent material of the second dopant compound may include one or more types of heavy metals among Ir, Pt and Pd.

[0023] The host compound may include one or more of mCP, mCBP, mCBP-CN, 2CzPy, DBFPO, DPEPO, DDBFT and pSiTrz, and may include two or more types of different host compounds.

[0024] A display apparatus according to still another embodiment of the present invention includes the organic light-emitting device.

[0025] A lighting apparatus according to yet another embodiment of the present invention includes the organic light-emitting device.

Advantageous Effects

[0026] A boron compound of the present invention reduces intermolecular packing characteristics using a specific substituent, and is effective in improving color characteristics in a device in a thin-film state while increasing quantum efficiency. In addition, an organic light-emitting device of the present invention is effective in improving color characteristics and lifespan characteristics by using the boron compound having improved stability through the substituent bond.

BRIEF DESCRIPTION OF DRAWINGS

[0027] FIG. 1a shows color characteristics of Example 1 of a boron compound of the present invention, and FIG. 1b shows exciton lifespan characteristics of Example 1 of the boron compound of the present invention.

[0028] FIG. 2a shows color characteristics of Example 2 of a boron compound of the present invention, and FIG. 2b shows exciton lifespan characteristics of Example 2 of the boron compound of the present invention.

[0029] FIG. 3a shows color characteristics of Example 3 of a boron compound of the present invention, and FIG. 3b shows exciton lifespan characteristics of Example 3 of the boron compound of the present invention.

[0030] FIG. 4a shows color characteristics of Example 4 of a boron compound of the present invention, and FIG. 4b shows exciton lifespan characteristics of Example 4 of the boron compound of the present invention.


BEST MODE

[0031] Hereinafter, the present invention will be described in detail with reference to drawings.

[0032] Prior thereto, terms or words used in the present specification and claims are not to be interpreted limitedly to common or dictionary meanings, and shall be interpreted as meanings and concepts corresponding to technical ideas of the present invention based on a principle in which inventors may suitably define the concept of terms in order to describe their invention in the best possible way.

[0033] Accordingly, embodiments described in the present specification and constitutions illustrated in the drawings are just most preferred one embodiment of the present invention, and do not represent all technical ideas of the present invention, and therefore, it needs to be understood that, at the time of filing of this application, there may be various equivalents and modified examples capable of replacing these.

[0034] A boron compound according to one aspect of the present invention is represented by the following Chemical Formula 1.






[0035] In Chemical Formula 1, X_1 to X_7 are each independently hydrogen, deuterium, a nitrile group, a halogen group, a substituted or unsubstituted $C_1\sim C_{10}$ alkyl group, a substituted or unsubstituted $C_3\sim C_{10}$ cycloalkyl group, a substituted or unsubstituted $C_1\sim C_{10}$ alkoxy group, a substituted or unsubstituted $C_1\sim C_{10}$ silyl group, a substituted or unsubstituted amine group, a substituted or unsubstituted $C_6\sim C_{20}$ aryl group, a substituted or unsubstituted $C_2\sim C_{20}$ heteroaryl group, a substituted or unsubstituted $C_{12}\sim C_{20}$ diarylamino group, a substituted or unsubstituted $C_4\sim C_{20}$ diheteroaryl amino group, or a substituted or unsubstituted $C_2\sim C_{20}$ arylheteroaryl amino group, Y_1 is N— R_4 , oxygen or sulfur, R_1 to R_3 are each independently hydrogen, deuterium, a nitrile group, a halogen group, a substituted or unsubstituted $C_1\sim C_{10}$ alkyl group, a substituted or unsubstituted $C_3\sim C_{10}$ cycloalkyl group, a substituted or unsubstituted $C_1\sim C_{10}$ alkoxy group, a substituted or unsubstituted $C_1\sim C_{10}$ silyl group, a substituted or unsubstituted amine group, a substituted or unsubstituted $C_6\sim C_{20}$ aryl group, a substituted or unsubstituted $C_2\sim C_{20}$ heteroaryl group, a substituted or unsubstituted $C_{12}\sim C_{20}$ diarylamino group, a substituted or unsubstituted $C_4\sim C_{20}$ diheteroaryl amino group, or a substituted or unsubstituted $C_2\sim C_{20}$ arylheteroaryl amino group, and R_4 is hydrogen, deuterium, a substituted or unsubstituted $C_1\sim C_{60}$ alkyl group, a substituted or unsubstituted $C_3\sim C_{10}$ cycloalkyl group, a substituted or unsubstituted $C_6\sim C_{60}$ aryl group, or a substituted or unsubstituted $C_6\sim C_{60}$ heteroaryl group.

[0036] The boron compound represented by Chemical Formula 1 is capable of preventing intermolecular interactions by increasing the intermolecular distance through attaching a rotating body or a bulky aromatic ring substituent to the end of the molecule in order to reduce an intermolecular packing phenomenon.

[0037] When a light-emitting compound of an organic light-emitting device exhibits intermolecular packing characteristics, a self-quenching phenomenon occurs, lowering quantum efficiency, and therefore, the boron compound represented by Chemical Formula 1 may have a substituent attached thereto in order to obtain the effect of increasing quantum efficiency. Specifically, when the boron core inner structure, which affects color characteristics, is transformed


into a carbazole form having only one side substituted with a heteroatom aromatic ring such as indole, furan or thiophene, while attaching a substituent capable of disrupting intermolecular packing at the para position of boron, which does not significantly affect color characteristics, the molecular structure exists in a distorted form while maintaining dark blue color characteristics, which may significantly reduce intermolecular packing. In addition, due to the increased conjugation length compared to before, effects of improving molecular stability and increasing quantum efficiency as well may be obtained.

[0038] The boron compound represented by Chemical Formula 1 may be, as a specific example, represented by one of the following Chemical Formulae 2 to 126.




-continued

[Chemical Formulae 5]




-continued


[Chemical Formulae 9]




[Chemical Formulae 6]



[Chemical Formulae 10]





[Chemical Formulae 7]




[Chemical Formulae 11]

[Chemical Formulae 8]




-continued

[Chemical Formulae 12]




-continued


[Chemical Formulae 15]




[Chemical Formulae 13]




[Chemical Formulae 16]



[Chemical Formulae 14]




[Chemical Formulae 17]




-continued

[Chemical Formulae 18]




-continued


[Chemical Formulae 21]




[Chemical Formulae 19]




[Chemical Formulae 22]



[Chemical Formulae 20]




[Chemical Formulae 23]




-continued


[Chemical Formulae 24]




[Chemical Formulae 25]



[Chemical Formulae 26]




[Chemical Formulae 27]




-continued


[Chemical Formulae 28]



[Chemical Formulae 29]




[Chemical Formulae 30]




-continued

[Chemical Formulae 31]




-continued


[Chemical Formulae 34]




[Chemical Formulae 32]




[Chemical Formulae 35]



[Chemical Formulae 33]




[Chemical Formulae 36]




-continued

[Chemical Formulae 37]




-continued


[Chemical Formulae 40]




[Chemical Formulae 38]




[Chemical Formulae 41]



[Chemical Formulae 39]




[Chemical Formulae 42]




-continued

[Chemical Formulae 43]




-continued


[Chemical Formulae 46]




[Chemical Formulae 44]




[Chemical Formulae 47]



[Chemical Formulae 45]




[Chemical Formulae 48]




-continued

[Chemical Formulae 49]




-continued


[Chemical Formulae 53]




[Chemical Formulae 50]




[Chemical Formulae 54]



[Chemical Formulae 52]




[Chemical Formulae 55]




-continued


[Chemical Formulae 56]




[Chemical Formulae 57]



[Chemical Formulae 58]




[Chemical Formulae 59]




-continued


[Chemical Formulae 60]



[Chemical Formulae 61]




[Chemical Formulae 62]




-continued

[Chemical Formulae 63]




-continued


[Chemical Formulae 67]




[Chemical Formulae 68]




[Chemical Formulae 64]




[Chemical Formulae 65]




[Chemical Formulae 66]



[Chemical Formulae 69]




[Chemical Formulae 70]




-continued

[Chemical Formulae 71]




-continued


[Chemical Formulae 74]




[Chemical Formulae 72]




[Chemical Formulae 75]



[Chemical Formulae 73]




[Chemical Formulae 76]




-continued

[Chemical Formulae 77]




-continued


[Chemical Formulae 80]



[Chemical Formulae 78]





[Chemical Formulae 81]




[Chemical Formulae 82]

[Chemical Formulae 79]




-continued


[Chemical Formulae 83]




[Chemical Formulae 84]



[Chemical Formulae 85]




[Chemical Formulae 86]




-continued


[Chemical Formulae 87]




[Chemical Formulae 88]



[Chemical Formulae 89]




[Chemical Formulae 90]




-continued


[Chemical Formulae 91]




[Chemical Formulae 92]



[Chemical Formulae 93]




[Chemical Formulae 94]




-continued


[Chemical Formulae 95]




[Chemical Formulae 96]



[Chemical Formulae 97]




[Chemical Formulae 98]




-continued

[Chemical Formulae 99]




-continued


[Chemical Formulae 103]




[Chemical Formulae 100]




[Chemical Formulae 101]




[Chemical Formulae 102]




[Chemical Formulae 104]



[Chemical Formulae 105]




[Chemical Formulae 106]




-continued

[Chemical Formulae 107]




-continued


[Chemical Formulae 110]




[Chemical Formulae 108]




[Chemical Formulae 111]




[Chemical Formulae 112]



[Chemical Formulae 109]




[Chemical Formulae 113]




-continued

[Chemical Formulae 114]




-continued


[Chemical Formulae 117]



[Chemical Formulae 118]




[Chemical Formulae 119]





[Chemical Formulae 120]

[Chemical Formulae 115]




[Chemical Formulae 116]




-continued

[Chemical Formulae 121]





-continued

[Chemical Formulae 124]





[Chemical Formulae 125]

[Chemical Formulae 122]



[Chemical Formulae 126]

[Chemical Formulae 123]




[0039] An organic light-emitting device according to another aspect of the present invention includes a first electrode, a second electrode provided opposite to the first electrode, and an organic material layer located between the first electrode and the second electrode, wherein the organic material layer includes the boron compound according to the present invention.

[0040] The organic material layer may have a single layer structure, but may preferably have a multilayer structure, and specifically, the organic material layer may include an electron injection layer (EIL), an electron transport layer (ETL), a light-emitting layer (EML), a hole transport layer (HTL) and a hole injection layer (HIL), and preferably, the boron compound may be a light emitter of the light-emitting layer (EML) and may specifically be a blue light emitter.

[0041] The light-emitting layer may include a host compound and a dopant compound that is a light emitter, and herein, the host compound may include an anthracene derivative represented by the following Chemical Formula 127.

[Chemical Formula 127]



[0042] In Chemical Formula 127, R_5 to R_{14} are each independently hydrogen, deuterium, a nitrile group, a halogen group, a substituted or unsubstituted C_1 ~ C_{10} alkyl group, a substituted or unsubstituted C_3 ~ C_{10} cycloalkyl group, a substituted or unsubstituted C_1 ~ C_{10} alkoxy group, a substituted or unsubstituted C_1 ~ C_{10} silyl group, a substituted or unsubstituted amine group, a substituted or unsubstituted C_6 ~ C_{20} aryl group, a substituted or unsubstituted C_2 ~ C_{20} heteroaryl group, a substituted or unsubstituted C_{12} ~ C_{20} diarylamino group, a substituted or unsubstituted C_4 ~ C_{20} diheteroarylamino group, or a substituted or unsubstituted C_2 ~ C_{20} arylheteroarylamino group, L_1 and L_2 are each independently a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group, and k s are each independently an integer of 1 to 3.

[0043] The light-emitting layer of the organic material layer includes a host compound, a first dopant compound and a second dopant compound, the second dopant compound is a delayed fluorescent material or a phosphorescent material, and the first dopant compound may be the boron compound according to the present invention. Herein, a half-width of the first dopant compound is preferably narrower than a half-width of the second dopant compound. Color purity increases as a half-width is narrower, and when the half-width of the first dopant compound that is a final light emitter is narrower than the half-width of the second dopant compound, there is an effect of obtaining device characteristics of high color purity compared to existing delayed fluorescent devices.

[0044] In the light-emitting layer, the host compound and the second dopant compound each preferably have higher singlet energy and triplet energy than the first dopant compound. The second dopant compound performs a role of

receiving energy from the host compound and transferring the energy to the first dopant compound, and a delayed fluorescent material having an electron donating-electron accepting structure or a heavy metal phosphorescent material is preferably used.

[0045] The delayed fluorescent material of the second dopant compound is a material having an electron acceptor-electron donor structure, and specific examples thereof may include materials using one or more of a boron compound, a triazine, a cyano group and a sulfone group as the electron acceptor and using one or more of a carbazole derivative and an acridane derivative as the electron donor, and the phosphorescent material of the second dopant compound may be a heavy metal, and specific examples thereof may include one or more types of heavy metals among Ir, Pt and Pd, however, the material is not limited to the above-described examples.

[0046] In addition, energy of the second dopant compound is transferred to the first dopant compound by the energy relationship between triplet and singlet of each dopant compound, and as the ratio of the first dopant compound receiving energy is smaller than that of the second dopant compound transferring energy, light emission efficiency of the first dopant compound that is a final light emitter may increase.

[0047] As the host compound transferring energy to the second dopant compound, host materials generally used in a light-emitting layer of an organic light-emitting device may be used, and as a specific example, host compounds including a carbazole such as mCP, mCBP, mCBP-CN or 2CzPy having triplet energy of 2.9 eV or greater, compounds including a phosphine oxide such as DBFPO or DPEPO, host materials including a triazine such as DDBFT or pSiTrz, and the like may be used, however, the compound is not limited to the above-described examples.

[0048] Herein, as the host compound, using two or more types of different host compounds may contribute to improving device characteristics such as efficiency and lifespan characteristics compared to using only one type of material. For example, when an electron-type host that favorably moves electrons and a host that favorably moves holes are used together, holes and electrons meet in a balanced manner inside the light-emitting layer, and high efficiency and lifespan characteristics may be expected. In addition, when a host that forms an exciplex is used, the driving voltage is lowered due to a small energy difference between the light-emitting layer and adjacent layers, excitons are widely formed inside the light-emitting layer while more energy is generated through a reverse intersystem crossing process between the host materials, which may improve device efficiency and lifespan characteristics.

[0049] The organic light-emitting device of the present invention has high color purity and excellent efficiency, and may thereby be used as a light-emitting device in various display apparatuses, and may be used in display apparatuses of, for example, TVs, smart phones, computers, automobiles and the like.

[0050] In addition, the organic light-emitting device of the present invention may be used in lighting apparatuses due to high efficiency.


[0051] Hereinafter, examples of the present invention will be described in detail so that those skilled in the art may readily implement the present invention. However, the pres-

ent invention may be implemented in various different forms, and is not limited to preparation examples and examples described herein.

Preparation Example: Synthesis of Boron Compound


Example 1: Synthesis of Boron Compound Represented by Chemical Formula 21

[0052] 2DPA (1 g, 2.2 mmol), NN (0.78 g, 2.34 mmol), $\text{Pd}_2(\text{dba})_3$ (0.023 g, 0.025 mmol), dicyclohexylphosphino 2',4',6'-triisopropylbiphenyl (0.024 g, 0.50 mmol) and NaOtBu (0.43 g, 4.5 mmol) were mixed in toluene, and stirred for 15 hours at 120° C. to allow a reaction as in the following Reaction Formula 1-1 to occur. When the reaction was finished, the reaction material was extracted using dichloromethane and water, and an organic layer was obtained. The organic layer was recrystallized using n-hexane to obtain a white solid intermediate 2DPA-NN (1.2 g).



[0053] After dissolving the 2DPA-NN (100 mg, 0.13 mmol) in 6 ml of o-dichlorobenzene at room temperature, boron tribromide (0.07 g, 0.27 mmol) was added thereto, and the result was stirred for 6 hours at 180° C. to allow a reaction as in the following Reaction Formula 1-2 to occur. When the reaction was finished, the reaction material was diluted with toluene, and filtered using a silica pad. After reducing the pressure, a white solid compound (Example 1) (52 mg) was obtained using a silica column.


[Reaction Formula 1-2]





Example 2: Synthesis of Boron Compound Represented by Chemical Formula 33

[0054] NO compound (1.3 g, 5.05 mmol) and 60% sodium hydride (13.8 mmol) were dissolved in 10 ml of a DMF solvent, and the mixture was slowly added to a DMF (5 ml) solution having 2DPA-F (2 g, 4.6 mmol) dissolved therein. The result was stirred for 15 hours at 150° C. to allow a reaction as in the following Reaction Formula 2-1 to occur. When the reaction was finished, the reaction material was poured into an ice bath and precipitated as a solid. The precipitated solid was extracted several times with water to obtain 2DPA-NO (0.62 g).



[Reaction Formula 2-1]



+



[Reaction Formula 2-2]




Example 2



Example 3: Synthesis of Boron Compound Represented by Chemical Formula 49

[0056] 2DPA (1 g, 2.2 mmol), NS (0.78 g, 2.27 mmol), $\text{Pd}_2(\text{dba})_3$ (0.023 g, 0.025 mmol), tri-*t*-butylphosphonium tetrafluoroborate (0.1 g, 0.34 mmol) and NaOtBu (0.43 g, 4.5 mmol) were dissolved in toluene, and stirred for 15 hours at 120° C. to allow a reaction as in the following Reaction Formula 3-1 to occur. When the reaction was finished, the reaction material was extracted using dichloromethane and water. The result was recrystallized and purified using *n*-hexane to obtain white solid 2DPA-NS (0.54 g).

[Reaction Formula 3-1]





[0055] After dissolving the 2DPA-NO (300 mg, 0.44 mmol) in 12 ml of *o*-dichlorobenzene at room temperature, boron tribromide (0.22 g, 0.90 mmol) was added thereto, and the result was stirred for 12 hours at 180° C. to allow a reaction as in the following Reaction Formula 2-2 to occur. When the reaction was completed, the reaction material was diluted with hot toluene, and filtered using a silica pad. After reducing the pressure, a white solid compound (Example 2) (167 mg) was obtained using a silica column.



[0057] After dissolving the 2DPA-NS (500 mg, 0.73 mmol) in 15 ml of o-dichlorobenzene, boron tribromide (0.36 g, 1.46 mmol) was added thereto, and the mixture was stirred for 10 hours at 180° C. to allow a reaction as in the following Reaction Formula 3-2 to occur. When the reaction was finished, the reaction material was filtered using a silica pad. After reducing the pressure, a white solid compound (Example 3) (186 mg) was obtained using a silica column.



[Reaction Formula 3-2]




Example 4: Synthesis of Boron Compound Represented by Chemical Formula 60



[0058] 2DPA-Cl (2 g, 2.2 mmol), NN (1.56 g, 2.27 mmol), Pd2 (dba) 3 (0.046 g, 0.025 mmol), tri-t-butylphosphonium tetrafluoroborate (0.2 g, 0.34 mmol) and NaOtBu (0.86 g, 4.5 mmol) were dissolved in toluene, and stirred for 10 hours at 90° C. to allow a reaction as in the following Reaction Formula 4-1 to occur. When the reaction was finished, the reaction material was extracted using dichloromethane and water. The result was recrystallized and purified using n-hexane to obtain white solid 2DPA-NN (1.08 g).

[Reaction Formula 4-1]






[0059] After dissolving the 2DPA-NN (650 mg, 0.73 mmol) in 15 ml of o-dichlorobenzene, boron tribromide (0.47 g, 1.46 mmol) was added thereto, and the mixture was stirred for 8 hours at 180° C. to allow a reaction as in the following Reaction Formula 4-2 to occur. When the reaction was finished, the reaction material was filtered using a silica pad. After reducing the pressure, a white solid compound (Example 4) (242 mg) was obtained using a silica column.





Example 5: Synthesis of Boron Compound Represented by Chemical Formula 100

[0060] 2DPA-Cl (1.18 g, 2.2 mmol), NN (0.92 g, 2.27 mmol), $\text{Pd}_2(\text{dba})_3$ (0.046 g, 0.015 mmol), tri-*t*-butylphosphonium tetrafluoroborate (0.12 g, 0.34 mmol) and NaOtBu (0.51 g, 4.5 mmol) were dissolved in toluene, and stirred for 10 hours at 90° C. to allow a reaction as in the following Reaction Formula 4-1 to occur. When the reaction was finished, the reaction material was extracted using dichloromethane and water. The result was recrystallized and purified using n-hexane to obtain white solid 2DPA-NO (0.64 g).

[Reaction Formula 5-1]





[0061] After dissolving the 2DPA-NO (650 mg, 0.73 mmol) in 15 ml of o-dichlorobenzene, boron tribromide (0.47 g, 1.46 mmol) was added thereto, and the mixture was stirred for 8 hours at 180° C. to allow a reaction as in the following Reaction Formula 5-2 to occur. When the reaction was finished, the reaction material was filtered using a silica pad. After reducing the pressure, a white solid compound (Example 5) (242 mg) was obtained using a silica column.

Experimental Example 1: Evaluation of Boron Compound Properties

[0062] Property evaluations were performed on Examples 1 to 5 prepared according to the above-described preparation examples. The properties were measured by a UV-Vis absorption spectrum and a room temperature photoluminescence spectrum, and the UV-Vis absorption spectrum was measured using JASCO V-750 by diluting the subject to a concentration of 10×10^{-5} M in a toluene solvent. As for the room temperature photoluminescence spectrum in a solution state, a condition of 10×10^{-4} M concentration in a toluene solvent was used, and as for the room temperature photoluminescence spectrum in a thin film state, an anthracene-based anthracene host was doped with 5% by weight of the compound for the preparation, and JASCO-FP 8500 equipment was used for the measurements. TRPL (Time-Resolved Photoluminescence) was measured using Hamamatsu C11367 equipment by diluting the subject to a concentration of 10×10^{-4} M in a dichloromethane solvent. Measurement results for each of Examples 1 to 4 are shown in FIG. 1a to FIG. 4b, and properties of DABNA-1 (Comparative Example 1), which is an existing material, and Examples 1 to 5 are compared in the following Table 1.

[Reaction Formula 5-2]




TABLE 1

Category	Comparative Example 1	Example 1	Example 2	Example 3	Example 4	Example 5
Compound Structure	DABNA-1	Chemical Formula 21	Chemical Formula 33	Chemical Formula 49	Chemical Formula 60	Chemical Formula 100
Maximum Absorption Spectrum	439 nm	443 nm	441 nm	443 nm	442 nm	445 nm

TABLE 1-continued

Category	Comparative Example 1	Example 1	Example 2	Example 3	Example 4	Example 5
Stokes' Shift	11 nm	18 nm	15 nm	17 nm	16 nm	16 nm
Maximum	450 nm	461 nm	456 nm	460 nm	458 nm	461 nm
Luminescence Spectrum (Solution)						
Half-Width (Solution)	21 nm	21 nm	22 nm	26 nm	22 nm	21 nm
Maximum	460 nm	466 nm	461 nm	465 nm	463 nm	466 nm
Luminescence Spectrum (Thin Film)						
Half-Width (Thin Film)	28 nm	25 nm	26 nm	31 nm	27 nm	26 nm
Singlet- Triplet Energy	0.20 eV	0.20 eV	0.20 eV	0.20 eV	0.24 eV	0.20 eV
Triplet Exciton Lifespan	93.7 μ s	4.45 μ s	7.04 μ s	9.76 μ s	5.17 μ s	6.15 μ s

[0063] As a result of the luminescence spectrum measurements, DABNA-1 that is Comparative Example 1 had the maximum luminescence peak increasing by 10 nm and the half-width by 7 nm in the thin film state compared to in the solution state, which worsened color characteristics, however, in Examples 1 to 5, the range of increase was only within 5 nm each.

Experimental Example 2: Evaluation on Delayed Fluorescent Device Including Boron Compound

[0064] An ITO glass substrate was cut to a size of 50 mm $\times$ 50 mm $\times$ 0.7 mm, washed using acetone, isopropyl


alcohol and distilled water for 10 minutes each, and then irradiated with ultraviolet rays for 10 minutes and exposed to ozone for cleaning. Then, the ITO glass substrate was installed on a vacuum deposition apparatus. On the ITO glass substrate, HATCN (7 nm)/TAPC (50 nm)/DCDPA (10 nm)/DBFPO host: 5% by weight of the boron compound (Example or Comparative Example) (25 nm)/DBFPO (5 nm)/TPBi (20 nm)/LiF (1.5 nm)/Al (100 nm) were laminated in this order to manufacture an organic light-emitting device. Device specific results are shown in the following Table 2.

TABLE 2

Category	Comparative Example 1	Example 1	Example 2	Example 3	Example 4	Example 5
Compound	DABNA-1	Chemical	Chemical	Chemical	Chemical	Chemical
Structure		Formula 21	Formula 33	Formula 49	Formula 60	Formula 100
Maximum	13.5%	19.3%	14.3%	16.7%	21.3%	15.1%
EQE (%)						
Half-Width (nm)	28 nm	21 nm	22 nm	26 nm	22 nm	21 nm
Maximum	460 nm	466 nm	461 nm	465 nm	463 nm	464 nm
Electro- lumines- cence Wavelength (nm)						
Device	2 Hours	3 Hours	3 Hours	5 Hours	6 Hours	4 Hours
Lifespan						
LT90						
@ 1,000 cd/m ² (Hour)						

[0065] Hereinbefore, examples of the present invention have been described in detail, however, the scope of a right of the present invention is not limited thereto, and it will be apparent to those skilled in the art that various modifications and variations may be made without departing technical ideas of the present invention described in the claims.

1. A boron compound represented by the following Chemical Formula 1:



wherein, in Chemical Formula 1,





X₁ to X₇ are each independently hydrogen, deuterium, a nitrile group, a halogen group, a substituted or unsubstituted C₁~C₁₀ alkyl group, a substituted or unsubstituted C₃~C₁₀ cycloalkyl group, a substituted or unsubstituted C₁~C₁₀ alkoxy group, a substituted or unsubstituted C₁~C₁₀ silyl group, a substituted or unsubstituted amine group, a substituted or unsubstituted C₆~C₂₀ aryl group, a substituted or unsubstituted C₂~C₂₀ heteroaryl group, a substituted or unsubstituted C₁₂~C₂₀ diarylamino group, a substituted or unsubstituted C₄~C₂₀ diheteroaryl amino group, or a substituted or unsubstituted C₂~C₂₀ arylheteroaryl amino group;

Y₁ is N—R₄, oxygen or sulfur;

R₁ to R₃ are each independently hydrogen, deuterium, a nitrile group, a halogen group, a substituted or unsubstituted C₁~C₁₀ alkyl group, a substituted or unsubstituted C₃~C₁₀ cycloalkyl group, a substituted or unsubstituted C₁~C₁₀ alkoxy group, a substituted or unsubstituted C₁~C₁₀ silyl group, a substituted or unsubstituted amine group, a substituted or unsubstituted C₆~C₂₀ aryl group, a substituted or unsubstituted C₂~C₂₀ heteroaryl group, a substituted or unsubstituted C₁₂~C₂₀ diarylamino group, a substituted or unsubstituted C₄~C₂₀ diheteroaryl amino group, or a substituted or unsubstituted C₂~C₂₀ arylheteroaryl amino group; and


R₄ is hydrogen, deuterium, a substituted or unsubstituted C₁~C₆₀ alkyl group, a substituted or unsubstituted C₃~C₁₀ cycloalkyl group, a substituted or unsubstituted C₆~C₆₀ aryl group, or a substituted or unsubstituted C₆~C₆₀ heteroaryl group.

2. The boron compound of claim 1, which is represented by one of the following Chemical Formulae 2 to 126:




-continued


[Chemical Formula 6]




[Chemical Formula 7]



[Chemical Formula 8]




[Chemical Formula 9]




-continued


[Chemical Formula 10]



[Chemical Formula 11]




[Chemical Formula 12]




-continued

[Chemical Formula 13]




-continued


[Chemical Formula 16]




[Chemical Formula 14]




[Chemical Formula 17]



[Chemical Formula 15]




[Chemical Formula 18]




-continued

[Chemical Formula 19]





-continued

[Chemical Formula 22]




[Chemical Formula 23]

[Chemical Formula 20]




[Chemical Formula 24]

[Chemical Formula 21]




[Chemical Formula 25]




-continued

[Chemical Formula 26]




-continued


[Chemical Formula 29]




[Chemical Formula 27]




[Chemical Formula 30]



[Chemical Formula 28]




[Chemical Formula 31]




-continued

[Chemical Formula 32]




-continued


[Chemical Formula 35]




[Chemical Formula 33]




[Chemical Formula 36]



[Chemical Formula 34]




[Chemical Formula 37]




-continued

[Chemical Formula 38]




-continued


[Chemical Formula 41]




[Chemical Formula 39]




[Chemical Formula 42]



[Chemical Formula 40]




[Chemical Formula 43]




-continued


[Chemical Formula 44]




[Chemical Formula 45]



[Chemical Formula 46]




[Chemical Formula 47]




-continued


[Chemical Formula 48]



[Chemical Formula 49]




[Chemical Formula 50]




-continued

[Chemical Formula 51]




-continued


[Chemical Formula 54]



[Chemical Formula 52]





[Chemical Formula 55]




[Chemical Formula 56]

[Chemical Formula 53]




-continued

[Chemical Formula 57]




-continued

[Chemical Formula 61]




[Chemical Formula 62]



[Chemical Formula 58]




[Chemical Formula 59]




[Chemical Formula 60]



[Chemical Formula 63]




[Chemical Formula 64]




-continued


[Chemical Formula 65]




[Chemical Formula 66]



[Chemical Formula 67]




[Chemical Formula 68]




-continued


[Chemical Formula 69]




[Chemical Formula 70]



[Chemical Formula 71]




[Chemical Formula 72]




-continued

[Chemical Formula 73]




-continued


[Chemical Formula 76]




[Chemical Formula 77]




[Chemical Formula 74]



[Chemical Formula 78]




[Chemical Formula 75]




-continued

[Chemical Formula 79]




-continued


[Chemical Formula 82]




[Chemical Formula 80]




[Chemical Formula 83]



[Chemical Formula 81]




[Chemical Formula 84]




-continued

[Chemical Formula 85]




-continued

[Chemical Formula 89]




[Chemical Formula 90]



[Chemical Formula 86]




[Chemical Formula 87]




[Chemical Formula 88]



[Chemical Formula 92]




[Chemical Formula 93]




-continued

[Chemical Formula 93]




-continued


[Chemical Formula 96]




[Chemical Formula 94]




[Chemical Formula 97]




[Chemical Formula 98]



[Chemical Formula 99]




[Chemical Formula 95]




-continued


[Chemical Formula 100]




[Chemical Formula 101]



[Chemical Formula 102]




[Chemical Formula 103]




-continued


[Chemical Formula 104]




[Chemical Formula 105]



[Chemical Formula 106]




[Chemical Formula 107]




-continued


[Chemical Formula 108]



[Chemical Formula 109]




[Chemical Formula 110]




-continued


[Chemical Formula 111]




[Chemical Formula 112]



[Chemical Formula 113]




[Chemical Formula 114]




-continued

[Chemical Formula 115]




-continued


[Chemical Formula 118]




[Chemical Formula 116]




[Chemical Formula 119]



[Chemical Formula 117]




[Chemical Formula 120]




-continued

[Chemical Formula 121]




-continued

[Chemical Formula 124]





[Chemical Formula 125]


[Chemical Formula 122]



[Chemical Formula 123]



[Chemical Formula 126]




3. An organic light-emitting device comprising:
 a first electrode;
 a second electrode provided opposite to the first electrode;
 and
 an organic material layer located between the first electrode and the second electrode,

wherein the organic material layer includes the boron compound of claim 1.

4. The organic light-emitting device of claim 3, wherein the organic material layer includes an electron injection layer (EIL), an electron transport layer (ETL), a light-emitting layer (EML), a hole transport layer (HTL) and a hole injection layer (HIL).

5. The organic light-emitting device of claim 4, wherein the light-emitting layer includes an anthracene derivative represented by the following Chemical Formula 127 as a host compound:

[Chemical Formula 127]



in Chemical Formula 127,

R_5 to R_{14} are each independently hydrogen, deuterium, a nitrile group, a halogen group, a substituted or unsubstituted $C_1\sim C_{10}$ alkyl group, a substituted or unsubstituted $C_3\sim C_{10}$ cycloalkyl group, a substituted or unsubstituted $C_1\sim C_{10}$ alkoxy group, a substituted or unsubstituted $C_1\sim C_{10}$ silyl group, a substituted or unsubstituted amine group, a substituted or unsubstituted $C_6\sim C_{20}$ aryl group, a substituted or unsubstituted $C_2\sim C_{20}$ heteroaryl group, a substituted or unsubstituted $C_{12}\sim C_{20}$ diarylamino group, a substituted or unsubstituted $C_4\sim C_{20}$ diheteroarylamino group, or a substituted or unsubstituted $C_2\sim C_{20}$ arylheteroarylamino group;

L_1 and L_2 are each independently a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group; and

k s are each independently an integer of 1 to 3.

6. The organic light-emitting device of claim 4, wherein the light-emitting layer includes a host compound, a first dopant compound and a second dopant compound;

the second dopant compound is a delayed fluorescent material or a phosphorescent material; and

the first dopant compound includes the boron compound of claim 1.

7. The organic light-emitting device of claim 6, wherein a half-width of the first dopant compound is narrower than a half-width of the second dopant compound.

8. The organic light-emitting device of claim 6, wherein the host compound and the second dopant compound each have higher singlet energy and triplet energy than the first dopant compound.

9. The organic light-emitting device of claim 6, wherein the delayed fluorescent material of the second dopant compound is a material having an electron donating-electron accepting structure;

the material having an electron donating-electron accepting structure uses one or more of a boron compound, a triazine, a cyano group and a sulfone group as an electron acceptor, and one or more of a carbazole derivative and an acridane derivative as an electron donor; and

the phosphorescent material of the second dopant compound includes one or more types of heavy metals among Ir, Pt and Pd.

10. The organic light-emitting device of claim 6, wherein the host compound includes one or more of mCP, mCBP, mCBP-CN, 2CzPy, DBFPO, DPEPO, DDBFT and pSiTrz.

11. The organic light-emitting device of claim 10, wherein the host compound includes two or more types of different host compounds.

12. A display apparatus comprising the organic light-emitting device of claim 3.

13. A lighting apparatus comprising the organic light-emitting device of claim 3.

14. An organic light-emitting device comprising:

a first electrode;

a second electrode provided opposite to the first electrode; and

an organic material layer located between the first electrode and the second electrode,

wherein the organic material layer includes the boron compound according to claim 2.

15. The organic light-emitting device of claim 14, wherein the organic material layer includes an electron injection layer (EIL), an electron transport layer (ETL), a light-emitting layer (EML), a hole transport layer (HTL) and a hole injection layer (HIL).

16. The organic light-emitting device of claim 15, wherein the light-emitting layer includes a host compound, a first dopant compound and a second dopant compound;

the second dopant compound is a delayed fluorescent material or a phosphorescent material;

and

the first dopant compound includes the boron compound according to claim 2.

* * * * *