

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250275397

Kind Code

A1

Publication Date

August 28, 2025

Inventor(s)

PARK; Mun Soo et al.

LIGHT EMITTING ELEMENT, DISPLAY DEVICE INCLUDING THE LIGHT EMITTING ELEMENT, AND ELECTRONIC DEVICE INCLUDING THE DISPLAY DEVICE

Abstract

A light emitting element includes a light emitting stack structure including a first semiconductor layer, a second semiconductor layer disposed below the first semiconductor layer, and an active layer disposed between the first semiconductor layer and the second semiconductor layer, a first bonding electrode disposed on the first semiconductor layer and electrically connected to the first semiconductor layer, and a second bonding electrode spaced apart from the first bonding electrode and electrically connected to the second semiconductor layer. The second bonding electrode covers at least a portion of a bottom surface of the light emitting stack structure.

Inventors: PARK; Mun Soo (Yongin-si, KR), KIM; Sung Hwan (Yongin-si, KR), SEO; Ji Youn (Yongin-si, KR)

Applicant: Samsung Display Co., LTD. (Yongin-si, KR)

Family ID: 1000008347848

Assignee: Samsung Display Co., LTD. (Yongin-si, KR)

Appl. No.: 18/973547

Filed: December 09, 2024

Foreign Application Priority Data

KR

10-2024-0028000

Feb. 27, 2024

Publication Classification

Int. Cl.: H10K59/131 (20230101); H10H29/49 (20250101); H10K59/80 (20230101)

U.S. Cl.:

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION(S)

[0001] This application claims priority to and benefits of Korean patent application No. 10-2024-0028000 under 35 U.S.C. § 119 filed on Feb. 27, 2024 in the Korean Intellectual Property Office, the entire contents of which are incorporated herein by reference.

BACKGROUND

1. Technical Field

[0002] The disclosure generally relates to a light emitting element, a display device including the light emitting element, and an electronic device including the display device.

2. Description of the Related Art

[0003] A display device is a device which displays an image by combining lights emitted from pixels. Each of the pixels may include at least one light emitting element emitting light.

[0004] In case that the efficiency of the light emitting element is improved, the display quality of an image displayed in the display device can be improved.

[0005] It is to be understood that this background of the technology section is, in part, intended to provide useful background for understanding the technology. However, this background of the technology section may also include ideas, concepts, or recognitions that were not part of what was known or appreciated by those skilled in the pertinent art prior to a corresponding effective filing date of the subject matter disclosed herein.

SUMMARY

[0006] Embodiments provide a light emitting element having improved efficiency and a display device including the light emitting element.

[0007] In accordance with an aspect of the disclosure, there is provided a light emitting element that may include a light emitting stack structure including a first semiconductor layer, a second semiconductor layer disposed below the first semiconductor layer, and an active layer disposed between the first semiconductor layer and the second semiconductor layer; a first bonding electrode disposed on the first semiconductor layer, the first bonding electrode electrically connected to the first semiconductor layer; and a second bonding electrode spaced apart from the first bonding electrode, the second bonding electrode electrically connected to the second semiconductor layer, wherein the second bonding electrode covers at least a portion of a bottom surface of the light emitting stack structure.

[0008] The second bonding electrode may directly cover the entire bottom surface of the light emitting stack structure.

[0009] The second semiconductor layer may include a first doping portion disposed below the active layer; and a second doping portion disposed below the first doping portion.

[0010] A first average doping concentration at the first doping portion may be greater than a second average doping concentration at the second doping portion.

[0011] A thickness of the second doping portion may be less than a thickness of the first doping portion.

[0012] The second semiconductor layer may include a first portion disposed below the active layer and overlapping the active layer in a plan view; and a second portion disposed below the first portion, the second portion having an area larger than an area of the first portion in a plan view.

[0013] The second bonding electrode may include a (2-1)th bonding electrode electrically connected to the second portion on the second portion not overlapping the first portion; and a (2-

2)th bonding electrode electrically contacting the (2-1)th bonding electrode, the (2-2)th bonding electrode covering at least a portion of the bottom surface of the light emitting stack structure while extending along a side surface of the second portion.

[0014] The first semiconductor layer, the active layer, and the first portion may overlap each other in a plan view.

[0015] The light emitting element may further include an insulative film covering at least a portion of an outer circumferential surface of the light emitting stack structure.

[0016] The first bonding electrode may be electrically connected to the first semiconductor layer through a first penetration hole defined in the insulative film. The second bonding electrode may be electrically connected to the second semiconductor layer through a second penetration hole defined in the insulative film.

[0017] The bottom surface of the light emitting stack structure may not be covered by the insulative film.

[0018] The light emitting element may further include an auxiliary electrode disposed between the first semiconductor layer and the first bonding electrode.

[0019] The first bonding electrode may electrically contact the auxiliary electrode.

[0020] The auxiliary electrode may directly cover an entire top surface of the first semiconductor layer.

[0021] In accordance with another aspect of the disclosure, there is provided a display device that may include an anode electrode disposed on a pixel circuit layer; a cathode electrode disposed on the pixel circuit layer; and a light emitting element disposed on the anode electrode and the cathode electrode, wherein the light emitting element may include a light emitting stack structure including a first semiconductor layer, a second semiconductor layer disposed below the first semiconductor layer, and an active layer disposed between the first semiconductor layer and the second semiconductor layer; a first bonding electrode disposed on the first semiconductor layer, the bonding electrode electrically connected to each of the first semiconductor layer and the anode electrode; and a second bonding electrode spaced apart from the first bonding electrode, the second bonding electrode electrically connected to each of the second semiconductor layer and the cathode electrode, and wherein the second bonding electrode covers at least a portion of a bottom surface of the light emitting stack structure.

[0022] The second bonding electrode may directly cover the entire bottom surface of the light emitting stack structure.

[0023] A portion of the second bonding electrode, which covers the bottom surface of the light emitting stack structure, may include a metal material.

[0024] In accordance with another aspect of the disclosure, there is provided a display device that may include an anode electrode disposed on a pixel circuit layer; a cathode electrode disposed on the pixel circuit layer; and a light emitting element disposed on the anode electrode and the cathode electrode, wherein the light emitting element may include a light emitting stack structure including a first semiconductor layer, a second semiconductor layer disposed on the first semiconductor layer, and an active layer disposed between the first semiconductor layer and the second semiconductor layer; a first bonding electrode disposed below the first semiconductor layer, the first bonding electrode electrically connected to each of the first semiconductor layer and the anode electrode; and a second bonding electrode spaced apart from the first bonding electrode, the second bonding electrode electrically connected to each of the second semiconductor layer and the cathode electrode, and wherein the second bonding electrode covers at least a portion of a top surface of the light emitting stack structure.

[0025] The second bonding electrode may directly cover the entire top surface of the light emitting stack structure.

[0026] A portion of the second bonding electrode, which covers the top surface of the light emitting stack structure, may include a metal oxide.

[0027] In accordance with another aspect of the disclosure, there is provided an electronic device that may include a processor to provide input image data; and a display device to display an image based on the input image data, wherein the display device may include an anode electrode disposed on a pixel circuit layer; a cathode electrode disposed on the pixel circuit layer; and a light emitting element disposed on the anode electrode and the cathode electrode, wherein the light emitting element may include a light emitting stack structure including a first semiconductor layer, a second semiconductor layer disposed below the first semiconductor layer, and an active layer disposed between the first semiconductor layer and the second semiconductor layer; a first bonding electrode disposed on the first semiconductor layer, the bonding electrode electrically connected to each of the first semiconductor layer and the anode electrode; and a second bonding electrode spaced apart from the first bonding electrode, the second bonding electrode electrically connected to each of the second semiconductor layer and the cathode electrode, and wherein the second bonding electrode covers at least a portion of a bottom surface of the light emitting stack structure.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0028] The above and other aspects and features of the disclosure will become more apparent by describing in detail embodiments thereof with reference to the attached drawings, in which:

[0029] FIG. 1 is a block diagram illustrating a display device in accordance with embodiments.

[0030] FIG. 2 is a block diagram illustrating any one sub-pixel among sub-pixels included in the display device shown in FIG. 1.

[0031] FIG. 3 is a schematic plan view illustrating a display panel constituting the display device shown in FIG. 1.

[0032] FIG. 4 is a sectional view illustrating an embodiment of the display panel shown in FIG. 3.

[0033] FIG. 5 is a sectional view illustrating an embodiment of the display panel shown in FIG. 3.

[0034] FIG. 6 is a schematic plan view illustrating an embodiment of a light emitting element included in a sub-pixel shown in FIG. 3.

[0035] FIG. 7 is a sectional view taken along line I1-I1' shown in FIG. 6.

[0036] FIG. 8 is a sectional view illustrating an embodiment of the light emitting element included in the sub-pixel shown in FIG. 3.

[0037] FIG. 9 is a schematic plan view illustrating an embodiment of a pixel to which the light emitting element shown in FIG. 6 is applied.

[0038] FIG. 10 is a sectional view taken along line Y1-Y1' shown in FIG. 9.

[0039] FIG. 11 is a sectional view taken along line X1-X1' shown in FIG. 9.

[0040] FIG. 12 is a schematic plan view illustrating an embodiment of the pixel to which the light emitting element shown in FIG. 6 is applied.

[0041] FIG. 13 is a sectional view taken along line Y2-Y2' shown in FIG. 12.

[0042] FIG. 14 is a sectional view taken along line X2-X2' shown in FIG. 12.

[0043] FIG. 15 is a block diagram illustrating a display system in accordance with an embodiment.

[0044] FIGS. 16 to 19 are schematic perspective views illustrating application examples of the display system shown in FIG. 15.

DETAILED DESCRIPTION OF THE EMBODIMENTS

[0045] Example embodiments will now be described more fully hereinafter with reference to the accompanying drawings; however, they may be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the example embodiments to those skilled in the art.

[0046] In the drawing figures, dimensions may be exaggerated for clarity of illustration. It will be

understood that when an element is referred to as being “between” two elements, it can be the only element between the two elements, or one or more intervening elements may also be present. Like reference numerals refer to like elements throughout.

[0047] In the entire specification, when an element is referred to as being “connected” or “coupled” to another element, it can be directly connected or coupled to the another element or be indirectly connected or coupled to the another element with one or more intervening elements disposed therebetween. The technical terms used herein are used only for the purpose of illustrating a given embodiment and not intended to limit the embodiment.

[0048] As used herein, the singular forms, “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

[0049] In the specification and the claims, the term “and/or” is intended to include any combination of the terms “and” and “or” for the purpose of its meaning and interpretation. For example, “A and/or B” may be understood to mean “A, B, or A and B.” The terms “and” and “or” may be used in the conjunctive or disjunctive sense and may be understood to be equivalent to “and/or.”

[0050] The terms “comprises,” “comprising,” “includes,” and/or “including,” “has,” “have,” and/or “having,” and variations thereof when used in this specification, specify the presence of stated features, integers, steps, operations, elements, components, and/or groups thereof, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

[0051] In the specification and the claims, the phrase “at least one of” is intended to include the meaning of “at least one selected from the group of” for the purpose of its meaning and interpretation. For example, “at least one of A and B” may be understood to mean “A, B, or A and B.”

[0052] It will be understood that, although the terms “first,” “second,” etc. may be used herein to describe various elements, these elements should not be limited by these terms. These terms are only used to distinguish one element from another element. Thus, a “first” element discussed below could also be termed a “second” element without departing from the teachings of the disclosure.

[0053] Spatially relative terms, such as “below,” “above,” and the like, may be used herein for ease of description to describe the relationship of one element to another element, as illustrated in the figures. It will be understood that the spatially relative terms, as well as the illustrated configurations, are intended to encompass different orientations of the apparatus in use or operation in addition to the orientations described herein and depicted in the figures. For example, if the apparatus in the figures is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, the term, “above,” may encompass both an orientation of above and below. The apparatus may be otherwise oriented (for example, rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein interpreted accordingly.

[0054] The terms “overlap” or “overlapped” mean that a first object may be above or below or to a side of a second object, and vice versa. Additionally, the term “overlap” may include layer, stack, face or facing, extending over, covering, or partly covering or any other suitable term as would be appreciated and understood by those of ordinary skill in the art.

[0055] The terms “face” and “facing” mean that a first element may directly or indirectly oppose a second element. In a case in which a third element intervenes between the first and second element, the first and second element may be understood as being indirectly opposed to one another, although still facing each other.

[0056] When an element is described as ‘not overlapping’ or ‘to not overlap’ another element, this may include that the elements are spaced apart from each other, offset from each other, or set aside from each other or any other suitable term as would be appreciated and understood by those of ordinary skill in the art.

[0057] The embodiments of the disclosure are described here with reference to schematic diagrams

(and an intermediate structure) of the disclosure, so that changes in a shape as shown due to, for example, manufacturing technology and/or a tolerance may be expected. Therefore, the embodiments of the disclosure shall not be limited to the illustrated shapes of a region shown here, but include shape deviations caused by, for example, the manufacturing technology. The regions shown in the drawings are schematic in nature, and the shapes thereof do not represent the actual shapes of the regions of the device, and do not limit the scope of the disclosure.

[0058] “About” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, “about” may mean within one or more standard deviations, or within $\pm 30\%$, 20% , 10% , 5% of the stated value.

[0059] Unless otherwise defined or implied herein, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which the disclosure pertains. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

[0060] Embodiments may be described and illustrated in the accompanying drawings in terms of functional blocks, units, and/or modules.

[0061] Those skilled in the art will appreciate that these blocks, units, and/or modules are physically implemented by electronic (or optical) circuits, such as logic circuits, discrete components, microprocessors, hard-wired circuits, memory elements, wiring connections, and the like, which may be formed using semiconductor-based fabrication techniques or other manufacturing technologies.

[0062] In the case of the blocks, units, and/or modules being implemented by microprocessors or other similar hardware, they may be programmed and controlled using software (for example, microcode) to perform various functions discussed herein and may optionally be driven by firmware and/or software.

[0063] It is also contemplated that each block, unit, and/or module may be implemented by dedicated hardware, or as a combination of dedicated hardware to perform some functions and a processor (for example, one or more programmed microprocessors and associated circuitry) to perform other functions.

[0064] Each block, unit, and/or module of embodiments may be physically separated into two or more interacting and discrete blocks, units, and/or modules without departing from the scope of the disclosure.

[0065] Further, the blocks, units, and/or modules of embodiments may be physically combined into more complex blocks, units, and/or modules without departing from the scope of the disclosure.

[0066] FIG. 1 is a block diagram illustrating a display device in accordance with embodiments.

[0067] Referring to FIG. 1, the display device DD may include a display panel DP, a gate driver **120**, a data driver **130**, a voltage generator **140**, and a controller **150**.

[0068] The display panel DP may include sub-pixels SP. The sub-pixels SP may be connected to the gate driver **120** through first to mth gate lines GL1 to GLm. The sub-pixels SP may be connected to the data driver **130** through first to nth data lines DL1 to DLn.

[0069] The sub-pixels SP may generate lights of two or more colors. For example, each of the sub-pixels SP may generate lights of red, green, blue, cyan, magenta, yellow, white, and the like within the spirit and the scope of the disclosure.

[0070] Two or more sub-pixels among the sub-pixels SP may constitute a pixel PXL. For example, the pixel PXL may include three sub-pixels as shown in FIG. 1. The pixel PXL may emit lights of various colors with various luminances according to a combination of lights emitted from the sub-pixels included in the pixel PXL.

[0071] The gate driver **120** may be connected to the sub-pixels SP (or disposed) in a row direction through the first to mth gate lines GL1 to GLm. The gate driver **120** may output gate signals to the first to mth gate lines GL1 to GLm in response to a gate control signal GCS. In embodiments, the gate control signal GCS may include a start signal indicating a start of each frame, a horizontal synchronization signal, and the like within the spirit and the scope of the disclosure.

[0072] The gate driver **120** may be disposed at one side or a side of the display panel DP. However, embodiments are not limited thereto. For example, the gate driver **120** may be divided into two or more drivers which are physically and/or logically divided, and these drivers may be disposed at one side or a side of the display panel DP and the other side of the display panel DP, which is opposite to the one side. or a side As such, in an embodiment, the gate driver **120** may be disposed in various forms at the periphery of the display panel DP.

[0073] The data driver **130** may be connected to the sub-pixels SP arranged in a column direction through the first to nth data lines DL1 to DLn. The data driver **130** may receive image data DATA and a data control signal DCS from the controller **150**. The data driver **130** may operate in response to the data control signal DCS. In embodiments, the data control signal DCS may include a source start pulse, a source shift clock, a source output enable signal, and the like within the spirit and the scope of the disclosure.

[0074] The data driver **130** may receive voltages from the voltage generator **140**. The data driver **130** may apply data signals having grayscale voltages corresponding to the image data DATA to the first to nth data lines DL1 to DLn by using the received voltages. In case that a gate signal is applied to each of the first to mth gate lines GL1 to GLm, data signals corresponding to the image data DATA may be applied to the first to nth data line DL1 to DLm. Accordingly, corresponding sub-pixels SP may generate light corresponding to the data signals. Accordingly, an image may be displayed on the display panel DP.

[0075] In embodiments, the gate driver **120** and the data driver **130** may include complementary metal-oxide semiconductor (CMOS) circuit elements.

[0076] The voltage generator **140** may operate in response to a voltage control signal VCS from the controller **150**. The voltage generator **140** may be configured to generate voltages and provide the generated voltages to components of the display device DD. The voltage generator **140** may generate voltages by receiving an input voltage from the outside of the display device DD and regulating the received voltage.

[0077] The voltage generator **140** may generate a first power voltage and a second power voltage. The generated first and second power voltages may be provided to the sub-pixels SP through power lines PL. In other embodiments, at least one of the first and second power voltages may be provided from the outside of the display device DD.

[0078] Besides, the voltage generator **140** may provide various voltages and/or signals. For example, the voltage generator **140** may provide one or more initialization voltages applied to the sub-pixels SP. For example, in a sensing operation for sensing electrical characteristics of transistors and/or light emitting elements of the sub-pixels SP, a selectable reference voltage may be applied to the first to nth data lines DL1 to DLn, and the voltage generator **140** may generate the reference voltage and transfer the reference voltage to the data driver **130**. For example, in a display operation for displaying an image on the display panel DP, common pixel control signals may be applied to the sub-pixels SP, and the voltage generator **140** may generate the pixel control signals. In embodiments, the voltage generator **140** may provide the pixel control signals to the sub-pixels SP through pixel control lines PXCL. In FIG. 1, it is illustrated that the pixel control lines PXCL are connected between the voltage generator **140** and the display panel DP. However, embodiments are not limited thereto. For example, the pixel control lines PXCL may be connected between the gate driver **120** and the display panel DP. The pixel control signals may be transferred to the sub-pixels SP from the gate driver **120** through the pixel control lines PXCL.

[0079] The controller **150** may control overall operations of the display device DD. The controller

150 may receive, from the outside, input image data IMG and a control signal CTRL corresponding thereto. The controller **150** may provide the gate control signal GCS, the data control signal DCS, and the voltage control signal VCS in response to the control signal CTRL.

[0080] The controller **150** may convert the input image data IMG to be suitable for the display device DD or the display panel DP, thereby outputting the image data DATA. In embodiments, the controller **150** may align the input image data IMG to be suitable for the sub-pixels SP in units of rows, thereby outputting the image data DATA.

[0081] Two or more components among the data driver **130**, the voltage generator **140**, and the controller **150** may be mounted on one integrated circuit. As shown in FIG. 1, the data driver **130**, the voltage generator **140**, and the controller **150** may be included in a driver integrated circuit DIC. The data driver **130**, the voltage generator **140**, and the controller **150** may be components functionally divided in one driver integrated circuit DIC. In other embodiments, at least one of the data driver **130**, the voltage generator **140**, and the controller **150** may be provided as a component distinguished from the driver integrated circuit DIC.

[0082] FIG. 2 is a block diagram illustrating any one sub-pixel among the sub-pixels included in the display device shown in FIG. 1. In FIG. 2, a sub-pixel SP_{ij} arranged on an ith row (i is an integer which is greater than or equal to 1 and is smaller than or equal to m) and a jth column (j is an integer which is greater than or equal to 1 and is smaller than or equal to n) among the sub-pixels SP shown in FIG. 1 is illustrated.

[0083] Referring to FIG. 2, the sub-pixel SP_{ij} may include a sub-pixel circuit SPC and a light emitting element LD.

[0084] The light emitting element LD may be connected between a first power voltage node VDDN and a second power voltage node VSSN. The first power voltage node VDDN may be connected to one of the power lines PL shown in FIG. 1, to receive a first power voltage. The second power voltage node VSSN may be connected to another of the power lines PL, to receive a second power voltage. The first power voltage may have a voltage level higher than a voltage level of the second power voltage.

[0085] The light emitting element LD may be connected between an anode electrode AE and a cathode electrode CE. The anode electrode AE may be connected to the first power voltage node VDDN through the sub-pixel circuit SPC. For example, the anode electrode AE may be connected to the first power voltage node VDDN through one or more transistors included in the sub-pixel circuit SPC. The cathode electrode CE may be connected to the second power voltage node VSSN. The light emitting element LD may be configured to emit light according to a current flowing from the anode electrode AE to the cathode electrode CE.

[0086] The sub-pixel circuit SPC may be connected to an ith gate line GL_i among the first to mth gate lines GL₁ to GL_m shown in FIG. 1 and a jth data line DL_j among the first to nth data lines DL₁ to DL_n shown in FIG. 1. In response to a gate signal received through the ith gate line GL_i, the sub-pixel circuit SPC may control the light emitting element LD to emit light according to a data signal received through the jth data line DL_j. In embodiments, the sub-pixel circuit SPC may be further connected to the pixel control lines PXCL shown in FIG. 1. The sub-pixel circuit SPC may control the light emitting element LD in further response to control signals received through the pixel control lines PXCL.

[0087] For these operations, the sub-pixel circuit SPC may include circuit elements, for example, transistors and one or more capacitors.

[0088] The transistors of the sub-pixel circuit SPC may include P-type transistors and/or N-type transistors. In embodiments, the transistors of the sub-pixel circuit SPC may include a Metal Oxide Silicon Field Effect Transistor (MOSFET). In embodiments, the transistors of the sub-pixel circuit SPC may include an amorphous silicon semiconductor, a monocrystalline silicon semiconductor, polycrystalline silicon semiconductor, an oxide semiconductor, and the like within the spirit and the scope of the disclosure.

[0089] FIG. 3 is a schematic plan view illustrating the display panel constituting the display device shown in FIG. 1.

[0090] Referring to FIG. 3, a display panel DP may include a display area DA and a non-display area NDA. The display panel DP displays an image through the display area DA. The non-display area NDA may be disposed at the periphery of the display area DA.

[0091] The display panel DP may include sub-pixels SP in the display area DA. The sub-pixels SP may be arranged in a first direction DR1 and a second direction DR2 intersecting the first direction DR1. For example, the sub-pixels SP may be arranged in a matrix form along the first direction DR1 and the second direction DR2. In another example, the sub-pixels SP may be arranged in a zigzag form along the first direction DR1 and the second direction DR2. The arrangement of the sub-pixels SP may vary in an embodiment. The first direction DR1 may be a row direction, and the second direction DR2 may be a column direction.

[0092] Two or more sub-pixels among the sub-pixels SP may constitute one pixel PXL. In FIG. 3, it is illustrated that the pixel PXL may include three sub-pixels SP1, SP2, and SP3. However, embodiments are not limited thereto. For example, the pixel PXL may include two sub-pixels. Hereinafter, for convenience of description, it is assumed that the pixel PXL may include first to third sub-pixels SP1, SP2, and SP3.

[0093] Each of the first to third sub-pixels SP1, SP2, and SP3 may generate light of one of various colors such as red, green, blue, cyan, magenta, and yellow. Hereinafter, for clear and simple description, it is assumed that the first sub-pixel SP1 is configured to generate light of a red color, the second sub-pixel SP2 is configured to generate light of a green color, and the third sub-pixel SP3 is configured to generate light of a blue color.

[0094] Each of the first to third sub-pixels SP1, SP2, and SP3 may include at least one light emitting element configured to generate light. In embodiments, light emitting elements of the first to third sub-pixels SP1, SP2, and SP3 may generate light of the same color. For example, the light emitting elements of the first to third sub-pixels SP1, SP2, and SP3 may generate light of a blue color. In other embodiments, the light emitting elements of the first to third sub-pixels SP1, SP2, and SP3 may generate lights of different colors. For example, the light emitting elements of the first to third sub-pixels SP1, SP2, and SP3 may generate lights a red color, a green color, and a blue color, respectively.

[0095] Self-luminous display panels, such as a light emitting diode display panel (LED display panel) using a light emitting diode of micro scale or nano scale as a light emitting element and an organic light emitting display panel (OLED panel) using an organic light emitting diode as a light emitting element, may be used as the display panel DP.

[0096] A component for controlling the sub-pixels SP may be disposed in the non-display area NDA. Lines connected to the sub-pixels SP, for example, the first to mth gate lines GL1 to GLm, the first to nth data lines DL1 to DLn, the power lines PL, and the pixel control lines PXCL, which are shown in FIG. 1, may be disposed in the non-display area NDA.

[0097] At least one of the gate driver 120, the data driver 130, the voltage generator 140, and the controller 150, which are shown in FIG. 1, may be disposed in the non-display area NDA of the display panel DP. In embodiments, the gate driver 120 may be disposed in the non-display area NDA. The data driver 150, the voltage generator 140, and the controller 150 may be implemented into the driver integrated circuit DIC shown in FIG. 1, which is distinguished from the display panel DP, and the driver integrated circuit DIC may be connected to the lines disposed in the non-display area NDA. In other embodiments, the gate driver 120, the data driver 130, the voltage generator 140, and the controller 150 may be implemented into one integrated circuit distinguished from the display panel DP.

[0098] In embodiments, the display area DA may have various shapes. The display area DA may have a closed-loop shape including linear sides and/or curved sides. For example, the display area DA may have shapes such as a polygon, a circle, a semicircle, and an ellipse.

[0099] In embodiments, the display panel DP may have a flat display surface. In other embodiments, the display panel DP may at least partially have a round display surface. In embodiments, the display panel DP may be bendable, foldable or rollable. The display panel DP and/or a substrate of the display panel DP may include materials having flexibility.

[0100] FIG. 4 is a sectional view illustrating an embodiment of the display panel shown in FIG. 3.

[0101] Referring to FIG. 4, a display panel DP may include a substrate SUB, and a pixel circuit layer PCL, a display panel layer DPL, and a light functional layer LFL, which may be sequentially stacked each other in a third direction DR3 intersecting the first and second directions DR1 and DR2 on the substrate SUB.

[0102] The substrate SUB may be made of an insulative material such as glass or resin. For example, the substrate SUB may include a glass substrate. In another example, the substrate SUB may include polyimide (PI) substrate. In another example, the substrate SUB may include a silicon wafer substrate formed using a semiconductor process.

[0103] In embodiments, the substrate SUB may be made of a material having flexibility to be curvable or foldable, and have a single-layer structure or a multi-layer structure. For example, the material having flexibility may include at least one of polystyrene, polyvinyl alcohol, polymethyl methacrylate, polyethersulfone, polyacrylate, polyetherimide, polyethylene naphthalate, polyethylene terephthalate, polyphenylene sulfide, polyarylate, polyimide, polycarbonate, triacetate cellulose, and cellulose acetate propionate. However, embodiments are not limited thereto.

[0104] The pixel circuit layer PCL may be disposed on the substrate SUB. The pixel circuit layer PCL may include insulating layers, and semiconductor patterns and conductive patterns, which are disposed between the insulating layers. The conductive patterns of the pixel circuit layer PCL may serve as circuit elements, lines, and the like within the spirit and the scope of the disclosure.

[0105] The circuit elements of the pixel circuit layer PCL may constitute a sub-pixel circuit SPC of each of the sub-pixels SP shown in FIG. 3. In other words, the circuit elements of the pixel circuit layer PCL may be provided as transistors and one or more capacitors of the sub-pixel circuit SPC.

[0106] The lines of the pixel circuit layer PCL may include lines connected to each of the sub-pixels SP. The lines of the pixel circuit layer PCL may include various signal lines and/or various voltage lines, which are for driving the display panel layer DPL.

[0107] The display panel layer DPL may be disposed on the pixel circuit layer PCL. The display panel layer DPL may include light emitting elements of the sub-pixels SP.

[0108] The light functional layer LFL may be disposed on the display panel layer DPL. The light functional layer LFL may include light conversion patterns having color conversion particles and/or light scattering particles. For example, color conversion particles may include quantum dots. The quantum dots may change a wavelength (or color) of light emitted from the display panel layer DPL. The light functional layer LFL may further include light scattering patterns having light scattering particles. In embodiments, the light conversion patterns and the light scattering patterns may be omitted.

[0109] The light functional layer LFL may further include a color filter layer including color filters. The color filter may allow light having a given wavelength (or given color) to be selectively transmitted therethrough. In embodiments, the color filter layer may be omitted.

[0110] A window for protecting an exposed surface (or top surface) of the display panel DP may be provided on the light functional layer LFL. The window may protect the display panel DP from external impact. The window may be bonded to the light functional layer LFL through an optically transparent adhesive (or cohesive) member. The window may have a multi-layer structure selected from a glass substrate, a plastic film, and a plastic substrate. This multi-layer structure may be formed through a continuous process or an adhesive process using an adhesive layer. The whole or a portion of the window may have flexibility.

[0111] FIG. 5 is a sectional view illustrating an embodiment of the display panel shown in FIG. 3.

[0112] Referring to FIG. 5, a display panel DP' may include a substrate SUB, a pixel circuit layer

PCL, a display panel layer DPL, an input sensing layer ISL, and a light functional layer LFL. The substrate SUB, the pixel circuit layer PCL, the display panel layer DPL, and the light functional layer LFL may be configured subsequently identical (or similar) to the substrate SUB, the pixel circuit layer PCL, the display panel layer DPL, and the light functional layer LFL, which are described with reference to FIG. 4, respectively. Therefore, descriptions of overlapping portions may be omitted.

[0113] The input sensing layer ISL may sense a user input with respect to a top surface (or display surface) of the display panel DP'. The input sensing layer ISL may include components suitable for sensing an external object such as a hand of a user or a pen. For example, the input sensing layer ISL may include touch electrodes.

[0114] FIG. 6 is a schematic plan view illustrating an embodiment of a light emitting element included in the sub-pixel shown in FIG. 3. FIG. 7 is a sectional view taken along line I1-I1' shown in FIG. 6.

[0115] Referring to FIGS. 6 and 7, a light emitting element LDa may include a light emitting stack structure EST, a first bonding electrode BDE1, a second bonding electrode BDE2, and an insulative film 40. The light emitting stack structure EST may include a first semiconductor layer 10, a second semiconductor layer 30 disposed under (or below) the first semiconductor layer 10, and an active layer 20 disposed between the first semiconductor layer 10 and the second semiconductor layer 30.

[0116] The first semiconductor layer 10 may be configured to provide holes. The first semiconductor layer 10 may have a first polarity. For example, the first semiconductor layer 10 may include at least one p-type semiconductor layer. For example, the first semiconductor layer 10 may include at least one semiconductor material among gallium nitride (GaN), aluminum gallium nitride (AlGaN), indium gallium nitride (InGaN), aluminum nitride (AlN), and indium nitride (InN), and be a p-type semiconductor layer doped with a first conductive dopant (or p-type dopant) such as magnesium (Mg), zinc (Zn), calcium (Ca), strontium (Sr) or barium (Ba). However, the material constituting the first semiconductor layer 10 is not limited thereto. Various materials may constitute the first semiconductor layer 10. In an embodiment, the first semiconductor layer 10 may include a gallium nitride (GaN) semiconductor material doped with the first conductive dopant (or n-type dopant).

[0117] The active layer 20 may be disposed between the first semiconductor layer 10 and the second semiconductor layer 30 to provide an area in which electrons and holes are recombined. As electrons and holes are recombined in the active layer 20, light may be generated, which has a level changed to a low energy level and has a wavelength corresponding to the low energy level. The active layer 20 may be formed in a single quantum well structure or a multi-quantum well structure. In case that the active layer 20 is formed in the multi-quantum well structure, a unit including a barrier layer, a strain reinforcing layer, and a well layer may be repeatedly stacked each other, to form the active layer 20. However, the active layer 20 is not limited to the above-described structure.

[0118] The second semiconductor layer 30 may be configured to provide electrons. The second semiconductor layer 30 may have a second polarity different from the first polarity. For example, the second semiconductor layer 30 may include at least one n-type semiconductor layer. For example, the second semiconductor layer 30 may include any one semiconductor material among gallium nitride (GaN), aluminum gallium nitride (AlGaN), indium gallium nitride (InGaN), aluminum nitride (AlN), and indium nitride (InN), and be an n-type semiconductor layer doped with a second conductive dopant (or n-type dopant) such as silicon (Si), germanium (Ge) or tin (Sn). However, the material constituting the second semiconductor layer 30 is not limited thereto. Various materials may constitute the second semiconductor layer 30. In an embodiment, the second semiconductor layer 30 may include a gallium nitride (GaN) semiconductor material doped with the second conductive dopant (or n-type dopant).

[0119] In an embodiment, the second semiconductor layer **30** may include a first doping portion **31** disposed under the active layer **20** and a second doping portion **32** disposed under the first doping portion **31**. The first doping portion **31** may be an area doped with a dopant at a relatively high concentration. The second doping portion **32** may be area doped with the dopant at a relatively low concentration or substantially undoped with the dopant. For example, a first average doping concentration at the first doping portion **31** may be greater than a second average doping concentration at the second doping portion **32**. The first doping portion **31** and the second doping portion **32** may be integral, to defining the second semiconductor layer **30**.

[0120] In embodiments, as shown in FIG. 7, the second semiconductor layer **30** may have a stepped shape including a first portion **30_P1** and a second portion **30_P2**.

[0121] The first portion **30_P1** may be disposed under the active layer **20**. The first portion **30_P1** may be a portion in direct contact with a bottom surface of the active layer **20**. The first portion **30_P1** may be disposed to substantially overlap the active layer **20** on a plane. That the first portion **30_P1** substantially overlaps the active layer on the plane may mean that a shape of the first portion **30_P1** on the plane completely overlaps a shape of the active layer **20** on the plane or that the shape of the first portion **30_P1** on the plane overlaps about 95% or more of the shape of the active layer **20** on the plane. In accordance with embodiments, the first semiconductor layer **10**, the active layer **20**, and the first portion **30_P1** may be disposed to substantially overlap each other on a plane.

[0122] The second portion **30_P2** may be disposed under the first portion **30_P1**. The second portion **30_P2** may have an area larger than an area of the first portion **30_P1** on a plane. At least a portion of the second portion **30_P2** may not overlap the first portion **30_P1** on the plane.

[0123] The first portion **30_P1** may be configured with a portion of the first doping portion **31** adjacent to the active layer **20**. The second portion **30_P2** may be configured with the other portion of the first doping portion **31** and the second doping portion **32**. The first portion **30_P1** and the second portion **30_P2** may be integral, to constitute the second semiconductor layer **30**.

[0124] The insulative film **40** may cover at least a portion of an outer circumferential surface of the light emitting stack structure EST. For example, the insulative film **40** may entirely cover the outer circumferential surface of the light emitting stack structure EST except a bottom surface of the light emitting stack structure EST. The insulative film **40** may include a transparent insulative material. The insulative film **40** may prevent an electric short circuit which may occur while the active layer **20** is in contact with another component having conductivity. In embodiments, the insulative film **40** may have a multi-layer structure including layers including a transparent insulative material.

[0125] The first bonding electrode BDE1 may be disposed on the first semiconductor layer **10**. The first bonding electrode BDE1 may be electrically connected to the first semiconductor layer **10**. For example, the first bonding electrode BDE1 may be electrically connected to the first semiconductor layer **10** through a first penetration hole CNT1 defined in the insulative film **40**. The first bonding electrode BDE1 may include, for example, a eutectic metal.

[0126] In accordance with embodiments, an auxiliary electrode SCE may be further disposed between the first bonding electrode BDE1 and the first semiconductor layer **10**. The auxiliary electrode SCE may be formed substantially transparent or translucent to satisfy a selectable light transmittance. For example, the auxiliary electrode SCE may include at least one of various transparent conductive materials such as indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), indium gallium zinc oxide (IGZO), and indium tin zinc oxide (ITZO). However, the material of the auxiliary electrode SCE is not limited thereto.

[0127] The auxiliary electrode SCE may directly cover an entire top surface of the first semiconductor layer **10**. The auxiliary electrode SCE may be disposed to substantially overlap the first semiconductor layer on a plane. The first bonding electrode BDE1 may be electrically in contact with the auxiliary electrode SCE through the first penetration hole CNT1 defined in the insulative film **40**. Accordingly, the first bonding electrode BDE1 may be electrically connected to

the first semiconductor layer **10** through the auxiliary electrode SCE. In embodiments, in case that the auxiliary electrode SCE is omitted, the first bonding electrode BDE1 may be electrically connected to the first semiconductor layer **10** through the first penetration hole CNT1 defined in the insulative film **40**.

[0128] The second bonding electrode BDE2 may be spaced apart from the first bonding electrode BDE1. The second bonding electrode BDE2 may be electrically connected to the second semiconductor layer **30**. Also, the second bonding electrode BDE2 may cover at least a portion of the bottom surface of the light emitting stack structure EST. At least a portion of the second bonding electrode BDE2 may face the first bonding electrode BDE1 with the light emitting stack structure EST disposed therebetween. For example, the second bonding electrode BDE2 may directly cover the entire bottom surface of the second doping portion **32**. Accordingly, a current density gradient in the active layer **20** can become relatively more uniform. Thus, the lifetime and emission distribution uniformity of the light emitting element LDa can be improved.

[0129] By way of example, a case where the second bonding electrode BDE2 is configured not to cover the bottom surface of the light emitting stack structure EST may be assumed. A current density in a partial area of the active layer **20** may become relatively high, and a current density of another partial area of the active layer **20** may become relatively low. For example, the current density gradient in the active layer **20** may be relatively non-uniform. Heat generation may occur in the area in which the current density in the active layer **20** is relatively high, and therefore, the light emitting element LDa may be degraded. The emission distribution uniformity of the light emitting element LDa may be deteriorated by the relatively non-uniform current density gradient in the active layer **20**.

[0130] In embodiments, the second bonding electrode BDE2 may include a (2-1)th bonding electrode BDE2-1 and a (2-2)th bonding electrode BDE2-2.

[0131] The (2-1)th bonding electrode BDE2-1 may be electrically connected to the second portion **30_P2** on the second portion **30_P2** not overlapping the first portion **30_P1**. For example, the (2-1)th bonding electrode BDE2-1 may be electrically in contact with the second portion **30_P2** through a second penetration hole CNT2 defined in the insulative film **40**. In embodiments, the (2-1)th bonding electrode BDE2-1 may be electrically connected to the first doping portion **31** having a relatively high average doping concentration. For example, the (2-1)th bonding electrode BDE2-1 may be electrically in contact with the first doping portion **31** exposed through the second penetration hole CNT2 defined in the insulative film **40**. The (2-1)th bonding electrode BDE2-1 may include a same material as the first bonding electrode BDE1, but the disclosure is not limited thereto.

[0132] The (2-2)th bonding electrode BDE2-2 may be electrically in contact with the (2-1)th bonding electrode BDE2-1. For example, the (2-1)th bonding electrode BDE2-1 may extend on the insulative film **40** covering a side surface of the second portion **30_P2** from the top of the second portion **30_P2**. The (2-2)th bonding electrode BDE2-2 may be in contact with an extending portion of the (2-1)th bonding electrode BDE2-1 on the insulative film **40** covering the side surface of the second portion **30_P2**. The (2-2)th bonding electrode BDE2-2 may extend on the insulative film **40** covering the side surface of the second portion **30_P2**, thereby covering at least a portion of the bottom surface of the light emitting stack structure EST.

[0133] The (2-2)th bonding electrode BDE2-2 may include a same material as the (2-1)th bonding electrode BDE2-1, but the disclosure is not limited thereto. For example, the (2-2)th bonding electrode BDE2-2 may be formed substantially transparent or translucent to satisfy a selectable light transmittance. The (2-2)th bonding electrode BDE2-2 may include at least one of various transparent conductive materials such as indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), indium gallium zinc oxide (IGZO), and indium tin zinc oxide (ITZO). In another example, the (2-2)th bonding electrode BDE2-2 may include a conductive material suitable for reflecting light. The light emission efficiency of the light emitting element LDa can be further

improved.

[0134] FIG. 8 is a sectional view illustrating an embodiment of the light emitting element included in the sub-pixel shown in FIG. 3. FIG. 8 is a sectional view taken along the line I1-I1' shown in FIG. 6.

[0135] Hereinafter, portions of a light emitting element LDa' shown in FIG. 8, which is different from those of the above-described light emitting element LDa, will be described, and portions of which description is omitted are the same as the above-described portions.

[0136] Referring to FIG. 8, a thickness T₃₂ of a second doping portion 32 in the third direction DR3 may be smaller than a thickness T₃₁ of a first doping portion 31. For example, the thickness T₃₂ of a second doping portion 32 in the third direction DR3 may be about 50% or less of the thickness T₃₁ of a first doping portion 31. Accordingly, as compared with the light emitting element LDa (see FIG. 7), a current density gradient in an active layer 20 of the light emitting element LDa' can become relatively more uniform.

[0137] Hereinafter, an embodiment in which each of the light emitting elements LDa and LDa' which have been described with reference to FIGS. 6 to 8 is provided as a lateral chip type light emitting element in the pixel PXL of the display panel DP (see FIG. 3) will be described with reference to FIGS. 9 to 11.

[0138] FIG. 9 is a schematic plan view illustrating an embodiment of a pixel to which the light emitting element shown in FIG. 6 is applied.

[0139] Referring to FIG. 9, a pixel PXL may include first to third sub-pixels SP1, SP2, and SP3.

The first to third sub-pixels SP1, SP2, and SP3 may be arranged in the first direction DR1.

However, the arrangement of the pixel PXL is not limited thereto, and may be variously changed in an embodiment. For example, the first to third sub-pixels SP1, SP2, and SP3 may be arranged in zigzag.

[0140] First to third anode electrodes AE1, AE2, and AE3 may be disposed in the first to third sub-pixels SP1, SP2, and SP3, respectively. The first anode electrode AE1 may be provided as an anode electrode AE (see FIG. 2) connected to a sub-pixel circuit SPC (see FIG. 2) of the first sub-pixel SP1. The second anode electrode AE2 may be provided as an anode electrode AE connected to a sub-pixel circuit SPC of the second sub-pixel SP2. The third anode electrode AE3 may be provided as an anode electrode AE connected to a sub-pixel circuit SPC of the third sub-pixel SP3.

[0141] A cathode electrode CE may be spaced apart from the first to third anode electrodes AE1, AE2, and AE3. The cathode electrode CE may be disposed at the same height as the first to third anode electrodes AE1, AE2, and AE3. The cathode electrode CE may be spaced apart from the first to third anode electrodes AE1, AE2, and AE3 in the second direction DR2. In embodiments, the cathode electrode CE may extend in the first direction DR1, to be used as a common electrode of the pixel PXL and other pixels adjacent to the pixel PXL. Although not shown in the drawing, the cathode electrode CE may extend in the second direction DR2 in addition to the first direction DR1, to be used as a common electrode of all the sub-pixels SP shown in FIG. 3. As such, the cathode electrode CE may have various shapes.

[0142] First to third light emitting elements LD1, LD2, and LD3 may be disposed on the first to third anode electrodes AE1, AE2, and AE3 and the cathode electrode CE. The first light emitting element LD1 may be electrically connected to the first anode electrode AE1 and the cathode electrode CE. The first light emitting element LD1 may be provided as a light emitting element LD (see FIG. 2) connected to the sub-pixel circuit SPC of the first sub-pixel SP1. The second light emitting element LD2 may be electrically connected to the second anode electrode AE2 and the cathode electrode CE. The second light emitting element LD2 may be provided as a light emitting element LD connected to the sub-pixel circuit SPC of the second sub-pixel SP2. The third light emitting element LD3 may be electrically connected to the third anode electrode AE3 and the cathode electrode CE. The third light emitting element LD3 may be provided as a light emitting element LD connected to the sub-pixel circuit SPC of the third sub-pixel SP3.

[0143] The first light emitting element LD1, the second light emitting element LD2, and the third light emitting element LD3 may be inorganic light emitting diodes including an inorganic light emitting material. The first light emitting element LD1, the second light emitting element LD2, and the third light emitting element LD3 may be configured substantially identical (or similar) to any one of the light emitting elements LDa and LDa' which have been described with reference to FIGS. 7 and 8.

[0144] FIG. 10 is a sectional view taken along line Y1-Y1' shown in FIG. 9.

[0145] Referring to FIGS. 9 and 10, a pixel circuit layer PCL, a display panel layer DPL, and a light functional layer LFL may be sequentially disposed on a substrate SUB.

[0146] The pixel circuit layer PCL may include insulating layers, semiconductor patterns, and conductive patterns, which may be stacked each other on the substrate SUB. The insulating layers may include a buffer layer BFL, one or more interlayer insulating layers ILD, and one or more passivation layers PSV1 and PSV2. The semiconductor patterns and the conductive patterns may be located (or disposed) between the insulating layers. The conductive patterns may include at least one material among copper (Cu), molybdenum (Mo), tungsten (W), aluminum neodymium (AlNd), titanium (Ti), aluminum (Al), and silver (Ag).

[0147] As described with reference to FIG. 2, the sub-pixel circuit SPC (see FIG. 2) of each of the first to third sub-pixels SP1, SP2, and SP3 may include transistors and capacitors. The semiconductor patterns and the conductive patterns of the pixel circuit layer PCL may serve as the transistors and the capacitors of the sub-pixel circuit SPC. The conductive patterns of the pixel circuit layer PCL may further serve as lines, for example, the first to mth gate lines GL1 to GLm, the first to nth data lines DL1 to DLn, the power lines PL, and the pixel control lines PXCL, which are shown in FIG. 1.

[0148] The buffer layer BFL may be disposed on one surface or s surface of the substrate SUB. The buffer layer BFL may prevent an impurity from being diffused into circuit elements and lines, which are included in the pixel circuit layer PCL. The buffer layer BFL may include an inorganic insulating layer including an inorganic material. In embodiments, the buffer layer BFL may include at least one of silicon nitride (SiN.sub.x), silicon oxide (SiO.sub.x), silicon oxynitride (SiO.sub.xN.sub.y), and a metal oxide such as aluminum oxide (AlO.sub.x). The buffer layer BFL may be provided as a single layer or a multi-layer. In case that the buffer layer BFL is provided as the multi-layer, layers of the multi-layer may be formed of a same material or be formed of different materials.

[0149] In embodiments, one or more barrier layers may be disposed between the substrate SUB and the buffer layer BFL. Each of the barrier layers may include polyimide.

[0150] A transistor T_SP may be disposed on the buffer layer BFL. The transistor T_SP may be any one of the transistors of the sub-pixel circuit SPC included in the first sub-pixel SPL. For example, the transistor T_SP may be understood as a transistor connected to a first anode electrode AE1 among the transistors of the sub-pixel circuit SPC.

[0151] The transistor T_SP may include a semiconductor pattern SCP, a gate electrode GE, a first terminal ET1, and a second terminal ET2. The first terminal ET1 may be any one of a source electrode and a drain electrode, and the second terminal ET2 may be the other of the source electrode and the drain electrode. For example, the first terminal ET1 may be the source electrode, and the second terminal ET2 may be the drain electrode.

[0152] The semiconductor pattern SCP may be disposed on the buffer layer BFL. The semiconductor pattern SCP may include a first contact region in contact with the first terminal ET1 and a second contact region in contact with the second terminal ET2. A region between the first contact region and the second contact region may be a channel region. The channel region may overlap the gate electrode GE of the transistor T_SP. The channel region is a semiconductor pattern substantially undoped with an impurity, and may be an intrinsic semiconductor. Each of the first contact region and the second contact region may be a semiconductor pattern doped with the

impurity. For example, a p-type impurity may be used as the impurity, but embodiments are not limited thereto.

[0153] The semiconductor pattern SCP may include any one of various types of semiconductors, for example, any one of an amorphous silicon semiconductor, a monocrystalline silicon semiconductor, a polycrystalline silicon semiconductor, a low temperature poly-silicon semiconductor, and an oxide semiconductor.

[0154] The sequentially stacked interlayer insulating layers ILD may be disposed over the semiconductor pattern SCP. The interlayer insulating layers ILD may be inorganic insulating layers including an inorganic material. For example, each of the interlayer insulating layers ILD may include at least one of silicon nitride, silicon oxide, silicon oxynitride, and a metal oxide such as aluminum oxide. However, the interlayer insulating layers ILD are not limited thereto. For example, any one of the interlayer insulating layers ILD may include an organic insulating layer including an organic material.

[0155] The interlayer insulating layers ILD may electrically separate the conductive patterns and/or the semiconductor patterns, which are disposed between the interlayer insulating layers ILD. For example, the interlayer insulating layers ILD may include a gate insulating layer GI disposed on the semiconductor pattern SCP. The gate insulating layer GI may be disposed between the semiconductor pattern SCP and the gate electrode GE such that the gate electrode GE is spaced apart from the semiconductor pattern SCP. In embodiments, the gate insulating layer GI may be entirely provided on the semiconductor pattern SCP and the buffer layer BFL, to cover the semiconductor pattern SCP and the buffer layer BFL. As the number of layers required to form the conductive patterns and/or the semiconductor patterns increases, the number of interlayer insulating layers ILD may increase.

[0156] The gate electrode GE may be disposed on the gate insulating layer GI. The gate electrode GE may overlap the channel region of the semiconductor pattern SCP. The gate electrode GE may be provided as a single layer including at least one material among copper (Cu), molybdenum (Mo), tungsten (W), aluminum neodymium (AlNd), titanium (Ti), aluminum (Al), and silver (Ag). In embodiments, the gate electrode GE may be provided as a multi-layer including at least one material among molybdenum (Mo), titanium (Ti), copper (Cu), aluminum (Al), and silver (Ag), which are low resistance materials.

[0157] The first and second terminals ET1 and ET2 may be disposed on the interlayer insulating layers ILD. The first and second terminals ET1 and ET2 may be in contact with the semiconductor pattern SCP through contact holes penetrating the interlayer insulating layers ILD. The first and second terminals ET1 and ET2 may be in contact with the first and second contact regions of the semiconductor pattern SCP, respectively. Each of the first and second terminals ET1 and ET2 may include at least one material among copper (Cu), molybdenum (Mo), tungsten (W), aluminum neodymium (AlNd), titanium (Ti), aluminum (Al), and silver (Ag).

[0158] In embodiments, the transistor T_SP may be configured as a low temperature poly-silicon transistor. However, embodiments are not limited thereto. For example, the transistor T_SP may be configured as an oxide semiconductor transistor. In embodiments, the sub-pixel circuit of the first sub-pixel SP1 may include different types of transistors. For example, the transistor T_SP may be configured as a low temperature poly-silicon transistor, and another transistor of the first sub-pixel SP1 may be configured as an oxide semiconductor transistor. An oxide semiconductor of the corresponding oxide semiconductor transistor may be disposed on any one of the interlayer insulating layers ILD instead of an insulating layer on which the semiconductor pattern SCP of the transistor T_SP.

[0159] In embodiments, a case where the transistor T_SP is a transistor having a top gate structure is described as an example. However, embodiments are not limited thereto. For example, the transistor T_SP may be a transistor having a bottom gate structure. The structure of the transistor T_SP may be variously changed.

[0160] At least a portion of various lines of the display panel DP and/or the display device DD may be further disposed on the interlayer insulating layers ILD.

[0161] A first passivation layer PSV1 may be disposed over the interlayer insulating layers ILD and the first and second terminals ET1 and ET2. The passivation layer may be designated as a protective layer or a via layer. The first passivation layer PSV1 may protect components disposed under the first passivation layer PSV1, and provide a flat top surface.

[0162] A connection pattern CP may be disposed on the first passivation layer PSV1. The connection pattern CP may be connected to the first terminal ET1 of the transistor T_SP while penetrating the first passivation layer PSV1. The connection pattern CP may include at least one material among copper (Cu), molybdenum (Mo), tungsten (W), aluminum neodymium (AlNd), titanium (Ti), aluminum (Al), and silver (Ag).

[0163] At least a portion of various lines of the display panel DP and/or the display device DD may be further disposed on the first passivation layer PSV1.

[0164] A second passivation layer PSV2 is disposed over the connection pattern CP and the first passivation layer PSV1. The second passivation layer PSV2 may protect components disposed under the second passivation layer PSV2, and provide a flat top surface.

[0165] Each of the first and second passivation layers PSV1 and PSV2 may include an inorganic insulating layer including an inorganic material and/or an organic insulating layer including an organic material. The inorganic insulating layer may include, for example, at least one of silicon oxide, silicon nitride, silicon oxynitride, and a metal oxide such as aluminum oxide. The organic insulating layer may include, for example, at least one of acrylic resin, epoxy resin, phenolic resin, polyamide resin, polyimide resin, unsaturated polyester resin, poly-phenylene ether resin, poly-phenylene sulfide resin, and benzocyclobutene resin.

[0166] The first and second passivation layers PSV1 and PSV2 may include a same material as any one of the interlayer insulating layers ILD, but embodiments are not limited thereto. Each of the first and second passivation layers PSV1 and PSV2 may be provided as a single layer, but be provided as a multi-layer.

[0167] The display panel layer DPL may be disposed on the second passivation layer PSV2. The display panel layer DPL may include the first anode electrode AE1, a cathode electrode CE, a first bank BNK1, first and second reflective electrodes RFE1 and RFE2, an overcoat layer OCL, a first light emitting element LD1, a third passivation layer PSV3, first and second transparent electrodes ITO1 and ITO2, and a capping layer CPL.

[0168] The first anode electrode AE1 and the cathode electrode CE may be disposed on the pixel circuit layer PCL.

[0169] The first anode electrode AE1 may be electrically connected to the connection pattern CP through a contact hole penetrating the second passivation layer PSV2. As such, the first anode electrode AE1 may be electrically connected to the transistor T_SP.

[0170] The cathode electrode CE may be spaced apart from the first anode electrode AE1 in the second direction DR1. The cathode electrode CE may be electrically connected to the second power voltage node VSSN shown in FIG. 2. Accordingly, the second power voltage applied to the second power voltage node VSSN may be transferred to the cathode electrode CE.

[0171] The first bank BNK1 may be disposed on the first anode electrode AE1 and the cathode electrode CE. The first bank BNK1 may have a first opening OP1 exposing portions of the first anode electrode AE1 and the cathode electrode CE. The first light emitting element LD1 may be disposed in the first opening OP1 of the first bank BNK1. As such, the first bank BNK1 may be provided as a pixel defining layer defining an area in which the first light emitting element LD1 is located.

[0172] The first bank BNK1 may be configured to include a light blocking material, to prevent light mixture between adjacent sub-pixels. In embodiments, the first bank BNK1 may include an organic material. For example, the first bank BNK1 may include an organic insulating material

such as acrylic resin, epoxy resin, phenolic resin, polyamide resin, or polyimide resin.

[0173] The first reflective electrode RFE1 may be disposed on the exposed portion of the first anode electrode AE1 and a side surface of the first bank BNK1, which is adjacent thereto. The second reflective electrode RFE2 may be disposed on the exposed portion of the cathode electrode CE and a side surface of the first bank BNK1, which is adjacent thereto. The first and second reflective electrodes RFE1 and RFE2 may include conductive materials suitable for reflecting light. Accordingly, the light emission efficiency of the first light emitting element LD1 can be improved. In embodiments, the first and second reflective electrodes RFE1 and RFE2 may include at least one of aluminum (Al), silver (Ag), magnesium (Mg), platinum (Pt), palladium (Pd), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), titanium (Ti), and alloys of two or more materials selected therefrom. However, embodiments are not limited thereto.

[0174] On the first and second reflective electrodes RFE1 and RFE2 and the second passivation layer PSV2, the overcoat layer OCL may be disposed in the first opening OP1 of the first bank BNK1. The first light emitting element LD1 on the overcoat layer OCL. The first light emitting element LD1 may be partially buried in the overcoat layer OCL.

[0175] The overcoat layer OCL may fix the first light emitting element LD1 not to move. Also, the overcoat layer OCL may protect components disposed under the overcoat layer OCL from a foreign matter such as dust or moisture. For example, the overcoat layer OCL may include at least one of an inorganic insulating layer and an organic insulating layer. For example, the overcoat layer OCL may include epoxy, but embodiments are not limited thereto.

[0176] The overcoat layer OCL may be disposed between a (2-2)th bonding electrode BDE2-2 of the first light emitting element LD1 and the first reflective electrode RFE1 and between the (2-2)th bonding electrode BDE2-2 and the second reflective electrode RFE2. Accordingly, the (2-2)th bonding electrode BDE2-2 may be spaced apart from each of the first reflective electrode RFE1 and the second reflective electrode RFE2.

[0177] The first light emitting element LD1 may include a light emitting stack structure EST, a first bonding electrode BDE1, a second bonding electrode BDE2, and an insulative film 40. The first light emitting element LD1 may be configured substantially identical (or similar) to any one of the light emitting elements LDa and LDa' which have been described with reference to FIGS. 6 to 8. The first light emitting element LD1 may be designated as a lateral chip type light emitting element. Hereinafter, descriptions of overlapping portions may be omitted.

[0178] In embodiments, in case that the first light emitting element LD1 is provided as the lateral chip type light emitting element, the (2-2)th bonding electrode BDE2-2 may include a conductive material suitable for reflecting light. For example, the (2-2)th bonding electrode BDE2-2 may include at least one of aluminum (Al), silver (Ag), magnesium (Mg), platinum (Pt), palladium (Pd), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), titanium (Ti), and alloys of two or more materials selected therefrom. However, embodiments are not limited thereto.

Accordingly, the light emission efficiency of the first light emitting element LD1 can be improved.

[0179] The third passivation layer PSV3 is disposed over the first and second reflective electrodes RFE1 and RFE2, the first light emitting element LD1, and the overcoat layer OCL. The third passivation layer PSV3 may protect components disposed under the third passivation layer PSV3, and provide a flat surface. The third passivation layer PSV3 may include a same material as any one of the first and second passivation layers PSV1 and PSV2, but embodiments are not limited thereto.

[0180] The third passivation layer PSV3 may have second to fifth openings OP2, OP3, OP4, and OP5. The second opening OP2 may expose a portion of the first reflective electrode RFE1. The third opening OP3 may expose the first bonding electrode BDE1. The fourth opening OP4 may expose a (2-1)th bonding electrode BDE2-1. The fifth opening OP5 may expose a portion of the second reflective electrode RFE2.

[0181] The first and second transparent electrodes ITO1 and ITO2 may be disposed on the third

passivation layer PSV3. The first transparent electrode ITO1 may electrically connect the first reflective electrode RFE1 exposed by the second opening OP2 to the first bonding electrode BDE1 exposed by the third opening OP3. The second transparent electrode ITO2 may electrically connect the (2-1)th bonding electrode BDE2-1 exposed by the fourth opening OP4 to the second reflective electrode RFE2 exposed by the fifth opening OP5. Accordingly, the first bonding electrode BDE1 may be electrically connected to the first anode electrode AE1 through the first transparent electrode ITO1 and the first reflective electrode RFE1. The second bonding electrode BDE2 may be electrically connected to the cathode electrode CE through the second transparent electrode ITO2 and the second reflective electrode RFE2.

[0182] In embodiments, the first and second transparent electrodes ITO1 and ITO2 may be formed substantially transparent or translucent to satisfy a selectable light transmittance. In embodiments, the first and second transparent electrodes ITO1 and ITO2 may include at least one of various transparent conductive materials such as indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), indium gallium zinc oxide (IGZO), and indium tin zinc oxide (ITZO). However, the material of the first and second transparent electrodes ITO1 and ITO2 is not limited thereto.

[0183] The capping layer CPL may be disposed on the third passivation layer PSV3. The capping layer CPL may protect components disposed under the capping layer CPL, such as the first and second transparent electrodes ITO1 and ITO2 and the first light emitting element LD1, from external moisture, humidity, and the like within the spirit and the scope of the disclosure. The capping layer CPL may include at least one of silicon nitride, silicon oxide, silicon oxynitride, and a metal oxide such as aluminum oxide. However, the material of the capping layer CPL is not limited thereto.

[0184] In the above, the pixel circuit layer PCL and the display panel layer DPL of the first sub-pixel SP1 have been described. Each of the second and third sub-pixels SP2 and SP3 shown in FIG. 8 may also be configured identically to the first sub-pixel SP1 in a range in which it is not differently described herein.

[0185] The light functional layer LFL may be disposed on the capping layer CPL. The light functional layer LFL may include the second bank BNK2, the reflective layer RFL, a fourth passivation layer PSV4, a first light conversion pattern CCP1, a low refractive layer LRL, and a color filter layer CFL.

[0186] The second bank BNK2 may be disposed on the capping layer CPL. The second bank BNK2 may overlap the first bank BNK1. The second bank BNK2 may have a sixth opening OP6 overlapping the first opening OP1.

[0187] The second bank BNK2 may be configured to include a light blocking material, to prevent light mixture between adjacent sub-pixels. In embodiments, the second bank BNK2 may include an organic material. For example, the second bank BNK2 may include an organic insulating material such as acrylic resin, epoxy resin, phenolic resin, polyamide resin, or polyimide resin.

[0188] The reflective layer RFL may be disposed on side surfaces of the second bank BNK2, which are adjacent to the sixth opening OP6. The reflective layer RFL is configured to reflect incident light, and accordingly, light emission efficiency can be improved. The reflective layer RFL may include a material suitable for reflecting light. The reflective layer RFL may include at least one of aluminum (Al), silver (Ag), magnesium (Mg), platinum (Pt), palladium (Pd), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), titanium (Ti), and alloys of two or more materials selected therefrom. However, embodiments are not limited thereto.

[0189] On the capping layer CPL, the fourth passivation layer PSV4 may be disposed in the sixth opening OP6. The fourth passivation layer PSV4 may protect components disposed under the fourth passivation layer PSV4, and provide a flat surface. The fourth passivation layer PSV4 may include a same material as any one of the first to third passivation layers PSV1 to PSV3, but embodiments are not limited thereto.

[0190] On the fourth passivation layer PSV4, the first light conversion pattern CCP1 may be

disposed in the sixth opening OP6.

[0191] The first light conversion pattern CCP1 may include color conversion particles and/or light scattering particles. The color conversion particles may convert incident light into light of another color by changing a wavelength of the incident light. Also, the color conversion particles may scatter incident light. In embodiments, the color conversion particles may be quantum dots. The light scattering particles may scatter incident light.

[0192] The first sub-pixel SP1 may be a red sub-pixel. In case that the first light emitting element LD1 emits light of a blue color, the first light conversion pattern CCP1 may include first color conversion particles QD1 configured to convert light of the blue color into light of a red color. In case that the first light emitting element LD1 emits light of the red color, the first light conversion pattern CCP1 may include light scattering particles. As such, the particles included in the first light conversion pattern CCP1 may be variously changed according to the first light emitting element LD1.

[0193] The low refractive layer LRL may be disposed on the second bank BNK2, the reflective layer RFL, and the first light conversion pattern CCP1. The low refractive layer LRL may have a refractive index lower than a refractive index of the first light conversion pattern CCP1. The low refractive layer LRL is configured to refract or totally reflect light according to an incident angle of the corresponding light. For example, the low refractive layer LRL may again provide light passing through the first light conversion pattern CCP1 to the first light conversion pattern CCP1.

Accordingly, the light conversion efficiency of the first light conversion pattern CCP1 can be improved.

[0194] The color filter layer CFL may be disposed on the low refractive layer LRL. The color filter layer CFL may include a first color filter CF1 and light blocking patterns LBP. The first color filter CF1 overlaps the first light conversion pattern CCP1. The first color filter CF1 may allow light in a desired wavelength range to be selectively transmitted therethrough. In case that the first sub-pixel SP1 is a red sub-pixel, the first color filter CF1 may include a red color filter. The light blocking patterns LBP may include at least one of various kinds of light blocking materials.

[0195] FIG. 11 is a sectional view taken along line X1-X1' shown in FIG. 9.

[0196] Referring to FIGS. 9 and 11, a pixel circuit layer PCL, a display panel layer DPL, and a light functional layer LFL may be provided on a substrate SUB.

[0197] The pixel circuit layer PCL and the display panel layer DPL are the same as described with reference to FIG. 10. In the pixel circuit layer PCL, sub-pixel circuits respectively corresponding to the first to third sub-pixels SP1, SP2, and SP3 are provided. In the display panel layer DPL, first to third light emitting elements LD1, LD2, and LD3 respectively corresponding to the first to third sub-pixels SP1, SP2, and SP3 may be provided. The first to third light emitting elements LD1, LD2, and LD3 may overlap first openings OP1 of a first bank BNK1. The first light emitting element LD1 may be connected between a cathode electrode CE (see FIG. 10) and a transistor T_SP (see FIG. 10) included in a sub-pixel circuit of the first sub-pixel SP1. The second light emitting element LD2 may be connected between the cathode electrode CE and a transistor included in a sub-pixel circuit of the second sub-pixel SP2. The third light emitting element LD3 may be connected between the cathode electrode CE and a transistor included in a sub-pixel circuit of the third sub-pixel SP3. Hereinafter, overlapping descriptions may be omitted.

[0198] The light functional layer LFL may be provided on the display panel layer DPL. The light functional layer LFL is the same as described with reference to FIG. 10. Hereinafter, overlapping descriptions may be omitted.

[0199] A second bank BNK2 may have sixth openings OP6. It may be understood that emission areas EMA and a non-emission area NEMA of the first to third sub-pixels SP1, SP2, and SP3 are defined by the second bank BNK2. An area overlapping the second bank BNK2 may correspond to the non-emission area NEMA. Areas overlapping the sixth openings OP6 of the second bank BNK2 may correspond to the emission areas EMA of the first to third sub-pixels SP1, SP2, and

SP3.

[0200] On a capping layer CPL, a fourth passivation layer PSV4 may be disposed in the sixth openings OP6. On the fourth passivation layer PSV4, first and second light conversion patterns CCP1 and CCP2 and a light scattering pattern LSP may be disposed in the sixth openings OP6.

[0201] In embodiments, the first to third light emitting elements LD1, LD2, and LD3 may be configured to emit light of a blue color. The first light conversion pattern CCP1 may include first color conversion particles QD1 configured to convert light of the blue color into light of a red color. The second light conversion pattern CCP2 may include second color conversion particles QD2 configured to convert light of the blue color into light of a green color. The light scattering pattern LSP may include light scattering particles SCT which scatter light of the blue color so as to improve light emission efficiency. Accordingly, the first to third sub-pixels SP1, SP2, and SP3 may be provided as a red sub-pixel, a green sub-pixel, and a blue sub-pixel, respectively. In embodiments, at least one of the first and second light conversion patterns CCP1 and CCP2 and the light scattering pattern LSP may further include color conversion patterns which convert light of the blue color into light of a white color.

[0202] In embodiments, the first to third light emitting elements LD1, LD2, and LD3 may be configured to emit lights of the red color, the green color, and the blue color, respectively. Each of the first and second light conversion patterns CCP1 and CCP2 and the light scattering pattern LSP may include the light scattering particles SCT. As such, the particles included in the first and second light conversion patterns CCP1 and CCP2 and the light scattering pattern LSP may be variously changed according to colors of lights emitted from the first to third light emitting elements LD1, LD2, and LD3.

[0203] In embodiments, the first and second light conversion patterns CCP1 and CCP2 and the light scattering pattern LSP may be omitted.

[0204] A low refractive layer LRL may be disposed on the second bank BNK2, a reflective layer RFL, the first light conversion pattern CCP1, the second light conversion pattern CCP2, and the light scattering pattern LSP. The low refractive layer LRL may have a refractive index lower than a refractive index of each of the first and second light conversion patterns CCP1 and CCP2 and the light scattering pattern LSP. In embodiments, the low refractive layer LRL may be omitted in an area corresponding to the third sub-pixel SP3.

[0205] A color filter layer CFL may be disposed on the low refractive layer LRL. The color filter layer CFL may include the first to third color filters CF1, CF2, and CF3 and light blocking patterns LBP.

[0206] Each of the first to third color filters CF1, CF2, and CF3 may allow light in a desired wavelength range to be selectively transmitted therethrough. In case that the first sub-pixel SP1 is a red sub-pixel, the first color filter CF1 may include a red color filter. In case that the second sub-pixel SP2 is a green sub-pixel, the second color filter CF2 may include a green color filter. In case that the third sub-pixel SP3 is a blue sub-pixel, the third color filter CF3 may include a blue color filter. The first to third color filters CF1, CF2, and CF3 may have a refractive index higher than the refractive index of the low refractive layer LRL. However, embodiments are not limited thereto, and the first to third color filters CF1, CF2, and CF3 may have a refractive index lower than or equal to the refractive index of the low refractive layer LRL.

[0207] The light blocking patterns LBP may be disposed between the color filters CF1, CF2, and CF3. It may be understood that the emission areas (or light output areas) EMA and the non-emission area NEMA of the first and second sub-pixels SP1, SP2, and SP3 are defined by the light blocking patterns LBP. An area overlapping the light blocking patterns LBP may correspond to the non-emission area NEMA. Areas not overlapping the light blocking patterns LBP may correspond to the emission areas EMA.

[0208] In embodiments, the light blocking patterns LBP may include at least one of various kinds of light blocking materials. In embodiments, each of the light blocking patterns LBP may be

provided in the form of a multi-layer overlapping at least two color filters among the first to third color filters CF1, CF2, and CF3. For example, each of the light blocking patterns LBP may be formed as the first to third color filters CF1, CF2, and CF3 overlap each other. In another example, a light blocking pattern between the first and second color filters CF1 and CF2 among the light blocking patterns LBP may be formed as a multi-layer in which the first and second color filters CF1 and CF2 overlap each other, and a light blocking pattern between the second and third color filters CF2 and CF3 among the light blocking patterns LBP may be formed as a multi-layer in which the second and third color filters CF2 and CF3 overlap each other. A light blocking pattern between the first color filter CF1 and a third color filter CF3 of an adjacent pixel may be formed as a multi-layer in which the first and third color filters CF1 and CF3 overlap each other. As such, each of the first to third color filters CF1, CF2, and CF3 may extend to the non-emission area NEMA to form the light blocking patterns LBP.

[0209] Hereinafter, an embodiment in which each of the light emitting elements LDa and LDa' which have been described with reference to FIGS. 6 to 8 is provided as a flip chip type light emitting element in a pixel PXL' of the display panel DP (see FIG. 3) will be described with reference to FIGS. 12 to 14.

[0210] FIG. 12 is a schematic plan view illustrating an embodiment of the pixel to which the light emitting element shown in FIG. 6 is applied.

[0211] Referring to FIG. 12, a pixel PXL' may include first to third sub-pixels SP1', SP2', and SP3'. The first to third sub-pixels SP1', SP2', and SP3' may be arranged in the first direction DR1. However, the arrangement of the pixel PXL' is not limited thereto, and may be variously changed in an embodiment. For example, the first to third sub-pixels SP1', SP2', and SP3' may be arranged in zigzag.

[0212] First to third anode electrodes AE1', AE2', and AE3' may be disposed in the first to third sub-pixels SP1', SP2', and SP3', respectively. The first anode electrode AE1' may be provided as an anode electrode AE (see FIG. 2) of a sub-pixel circuit SPC (see FIG. 2) of the first sub-pixel SP1'. The second anode electrode AE2' may be provided as an anode electrode AE of a sub-pixel circuit SPC of the second sub-pixel SP2'. The third anode electrode AE3' may be provided as an anode electrode AE of a sub-pixel circuit SPC of the third sub-pixel SP3'.

[0213] A cathode electrode CE' may be spaced apart from the first to third anode electrodes AE1', AE2', and AE3'. The cathode electrode CE' may be disposed at the same height as the first to third anode electrodes AE1', AE2', and AE3'. The cathode electrode CE' may be spaced apart from the first to third anode electrodes AE1', AE2', and AE3' in the second direction DR2. In embodiments, the cathode electrode CE' may extend in the first direction DR1, to be used as a common electrode of the pixel PXL' and other pixels adjacent to the pixel PXL'. Although not shown in the drawing, the cathode electrode CE' may extend in the second direction DR2 in addition to the first direction DR1, to be used as a common electrode of all the sub-pixels SP shown in FIG. 3. As such, the cathode electrode CE' may have various shapes.

[0214] First to third light emitting elements LD1', LD2', and LD3' may be disposed on the first to third anode electrodes AE1', AE2', and AE3' and the cathode electrode CE'. The first light emitting element LD1' may be electrically connected to the first anode electrode AE1' and the cathode electrode CE'. The first light emitting element LD1' may be provided as a light emitting element LD (see FIG. 2) connected to the sub-pixel circuit SPC of the first sub-pixel SP1'. The second light emitting element LD2' may be electrically connected to the second anode electrode AE2' and the cathode electrode CE'. The second light emitting element LD2' may be provided as a light emitting element LD connected to the sub-pixel circuit SPC of the second sub-pixel SP2'. The third light emitting element LD3' may be electrically connected to the third anode electrode AE3' and the cathode electrode CE'. The third light emitting element LD3' may be provided as a light emitting element LD connected to the sub-pixel circuit SPC of the third sub-pixel SP3'.

[0215] The first light emitting element LD1', the second light emitting element LD2', and the third

light emitting element LD3' may be inorganic light emitting diodes including an inorganic light emitting material. For example, the first light emitting element LD1', the second light emitting element LD2', and the third light emitting element LD3' may be configured substantially identical (or similar) to any one of the light emitting elements LDa and LDa' which have been described with reference to FIGS. 7 and 8.

[0216] FIG. 13 is a sectional view taken along line Y2-Y2' shown in FIG. 12.

[0217] Referring to FIGS. 12 and 13, a pixel circuit layer PCL, a display panel layer DPL, and a light functional layer LFL may be sequentially disposed on a substrate SUB.

[0218] The pixel circuit layer PCL may be configured substantially identically as has been described with reference to FIG. 10. Therefore, overlapping descriptions may be omitted.

[0219] The display panel layer DPL may be disposed on the pixel circuit layer PCL. The display panel layer DPL may include a first anode electrode AE1', a cathode electrode CE', a first bank BNK1, first and second reflective electrodes RFE1 and RFE2, a first light emitting element LD1', an overcoat layer OCL, a third passivation layer PSV3, and a capping layer CPL.

[0220] The first anode electrode AE1' and the cathode electrode CE' may be disposed on the pixel circuit layer PCL.

[0221] The first anode electrode AE1' may be electrically connected to a connection pattern CP through a contact hole penetrating a second passivation layer PSV2. As such, the first anode electrode AE1' may be electrically connected to a transistor T_SP.

[0222] The cathode electrode CE' may be spaced apart from the first anode electrode AE1' in the second direction DR2. The cathode electrode CE' may be electrically connected to the second power voltage node VSSN shown in FIG. 2. Accordingly, the second power voltage applied to the second power voltage node VSSN may be transferred to the cathode electrode CE'.

[0223] The first bank BNK1 may be disposed on the first anode electrode AE1' and the cathode electrode CE'. The first bank BNK1 may have a first opening OP1 exposing portions of the first anode electrode AE1' and the cathode electrode CE'. The first light emitting element LD1' may be disposed in the first opening OP1 of the first bank BNK1. As such, the first bank BNK1 may be provided as a pixel defining layer defining an area in which the first light emitting element LD1' is located.

[0224] The first bank BNK1 may be configured to include a light blocking material, to prevent light mixture between adjacent sub-pixels. In embodiments, the first bank BNK1 may include an organic material. For example, the first bank BNK1 may include an organic insulating material such as acrylic resin, epoxy resin, phenolic resin, polyamide resin, or polyimide resin.

[0225] The first reflective electrode RFE1 may be disposed on the exposed portion of the first anode electrode AE1' and a side surface of the first bank BNK1, which is adjacent thereto. The second reflective electrode RFE2 may be disposed on the exposed portion of the cathode electrode CE' and a side surface of the first bank BNK1, which is adjacent thereto. The first and second reflective electrodes RFE1 and RFE2 may include conductive materials suitable for reflecting light. Accordingly, the light emission efficiency of the first light emitting element LD1' can be improved. In embodiments, the first and second reflective electrodes RFE1 and RFE2 may include at least one of aluminum (Al), silver (Ag), magnesium (Mg), platinum (Pt), palladium (Pd), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), titanium (Ti), and alloys of two or more materials selected therefrom. However, embodiments are not limited thereto.

[0226] The first light emitting element LD1' may be configured substantially identical (or similar) to any one of the light emitting elements LDa and LDa' which have been described with reference to FIGS. 6 to 8. For example, the first light emitting element LD1' is one obtained by turning upside down the first bonding electrode BDE1 and the (2-1)th bonding electrode BDE2-1 of the light emitting element LDa to face the first anode electrode AE1' and the cathode electrode CE'. More specifically, a light emitting stack EST' may include a first semiconductor layer 10', a second semiconductor layer 30' disposed on the first semiconductor layer 10', and an active layer 20'

disposed between the first semiconductor layer **10'** and the second semiconductor layer **30'**. The second semiconductor layer **30'** may include a first doping portion **31'** and a second doping portion **32'** disposed on the first doping portion **31'**. A first bonding electrode **BDE1'** may be disposed under (or below) the first semiconductor layer **10'**. A second bonding electrode **BDE2'** may be spaced apart from the first bonding electrode **BDE1'**, and may cover at least a portion of a top surface of the light emitting stack structure **EST'**. The second bonding electrode **BDE2'** may include a (2-1)th bonding electrode **BDE2-1'** and a (2-2)th bonding electrode **BDE2-2'**. An insulative film **40'** may cover at least a portion of an outer circumferential surface of the light emitting stack structure **EST'**. An auxiliary electrode **SCE'** may be disposed between the first bonding electrode **BDE1'** and the first semiconductor layer **10'**. The first light emitting element **LD1'** may be designated as a flip chip type light emitting element. Hereinafter, descriptions of overlapping portions may be omitted.

[0227] The first light emitting element **LD1'** may be electrically connected to the first anode electrode **AEL1'**. For example, the first light emitting element **LD1'** may further include a first connection electrode **CNE1**. The first connection electrode **CNE1** may be bonded to the first bonding electrode **BDE1'**. The first connection electrode **CNE1** may be electrically in contact with each of the first bonding electrode **BDE1'** and the first reflective electrode **RFE1**. Accordingly, the first light emitting element **LD1'** may be electrically connected to the first anode electrode **AE1'** through the first connection electrode **CNE1** and the first reflective electrode **RFE1**.

[0228] The first light emitting element **LD1'** may be electrically connected to the cathode electrode **CE'**. For example, the first light emitting element **LD1'** may further include a second connection electrode **CNE2**. The second connection electrode **CNE2** may be bonded to the (2-1)th bonding electrode **BDE2-1'**. The second connection electrode **CNE2** may be electrically in contact with each of the (2-1)th bonding electrode **BDE2-1'** and the second reflective electrode **RFE2**. Accordingly, the first light emitting element **LD1'** may be electrically connected to the cathode electrode **CE'** through the second connection electrode **CNE2** and the second reflective electrode **RFE2**.

[0229] In embodiments, the first and second connection electrodes **CNE1** and **CNE2** may include a same material as the first bonding electrode **BDE1'** and the (2-1)th bonding electrode **BDE2-1'**, but embodiments are not limited thereto.

[0230] In embodiments, in case that the first light emitting element **LD1'** is provided as the flip chip type light emitting element, the (2-2)th bonding electrode **BDE2-2'** may be formed substantially transparent or translucent to satisfy a selectable light transmittance. Accordingly, light emitted from the first light emitting element **LD1'** is not substantially blocked by the (2-2)th bonding electrode **BDE2-2'**, but may be provided to the light functional layer **LFL**. In embodiments, the (2-2)th bonding electrode **BDE2-2'** may include at least one of various transparent conductive materials such as indium tin oxide (**ITO**), indium zinc oxide (**IZO**), zinc oxide (**ZnO**), indium gallium zinc oxide (**IGZO**), and indium tin zinc oxide (**ITZO**). However, the material of the (2-2)th bonding electrode **BDE2-2'** is not limited thereto.

[0231] The overcoat layer **OCL** may be disposed in the first opening in which the first and second reflective electrodes **RFE1** and **RFE2** and the first light emitting element **LD1'** are disposed. The overcoat layer **OCL** may fix the first light emitting element **LD1'** bonded to the first and second reflective electrodes **RFE1** and **RFE2** not to move. Also, the overcoat layer **OCL** may protect components disposed under the overcoat layer **OCL** from a foreign matter such as dust or moisture. For example, the overcoat layer **OCL** may include at least one of an inorganic insulating layer and an organic insulating layer. For example, the overcoat layer **OCL** may include epoxy, but embodiments are not limited thereto.

[0232] The third passivation layer **PSV3** is disposed over the first bank **BNK1** and the overcoat layer **OCL**. The third passivation layer **PSV3** may protect components disposed under the third passivation layer **PSV3**, and provide a flat surface. The third passivation layer **PSV3** may include a

same material as any one of a first passivation layer PSV1 and the second passivation layer PSV2, but embodiments are not limited thereto.

[0233] In embodiments, the third passivation layer PSV3 may not be disposed on a top surface of the first light emitting element LD1'. In other words, the third passivation layer PSV may not be disposed on the (2-2)th bonding electrode BDE2-2' covering at least a portion of a top surface of the second doping portion 32'. The first light emitting element LD1' may protrude to the light functional layer LFL. The first light emitting element LD1' may be at least partially located in a second opening OP2 of a second bank BNK2. For example, a height of the top surface of the first light emitting element LD1' from the substrate SUB may be higher than a height of a lowermost end of a reflective layer RFL from the substrate SUB. Accordingly, light emitted from the first light emitting element LD1' may be provided to the light functional layer LFL at a relatively high rate.

[0234] The capping layer CPL may be disposed on the third passivation layer PSV3. The capping layer CPL may protect components disposed under the capping layer CPL, such as the first light emitting element LD1', from external moisture, humidity, and the like within the spirit and the scope of the disclosure. In embodiments, the capping layer CPL may not be disposed on the top surface of the first light emitting element LD1'. In other embodiments, the capping layer CPL may entirely cover the first light emitting element LD1' and the third passivation layer PSV3. The capping layer CPL may include at least one of silicon nitride, silicon oxide, silicon oxynitride, and a metal oxide such as aluminum oxide. However, the material of the capping layer CPL is not limited thereto.

[0235] In the above, the pixel circuit layer PCL and the display panel layer DPL of the first sub-pixel SP1' have been described. Each of the second and third sub-pixels SP2' and SP3' shown in FIG. 12 may also be configured identically to the first sub-pixel SP1' in a range in which it is not differently described herein.

[0236] The light functional layer LFL may be disposed on the capping layer CPL. The light functional layer LFL may include the second bank BNK2, the reflective layer RFL, a fourth passivation layer PSV4, a first light conversion pattern CCP1, a low refractive layer LRL, and a color filter layer CFL.

[0237] The second bank BNK2 may be disposed on the capping layer CPL. The second bank BNK2 may overlap the first bank BNK1. The second bank BNK2 may have the second opening OP2 overlapping the first opening OP1.

[0238] The second bank BNK2 may be configured to include a light blocking material, to prevent light mixture between adjacent sub-pixels. In embodiments, the second bank BNK2 may include an organic material. For example, the second bank BNK2 may include an organic insulating material such as acrylic resin, epoxy resin, phenolic resin, polyamide resin, or polyimide resin.

[0239] The reflective layer RFL may be disposed on side surfaces of the second bank BNK2, which are adjacent to the second opening OP2. The reflective layer RFL is configured to reflect incident light, and accordingly, light emission efficiency can be improved. The reflective layer RFL may include a material suitable for reflecting light. The reflective layer RFL may include at least one of aluminum (Al), silver (Ag), magnesium (Mg), platinum (Pt), palladium (Pd), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), titanium (Ti), and alloys of two or more materials selected therefrom. However, embodiments are not limited thereto.

[0240] On the capping layer CPL, the fourth passivation layer PSV4 may be disposed in the second opening OP2. The fourth passivation layer PSV4 may protect components disposed under the fourth passivation layer PSV4, and provide a flat surface. The fourth passivation layer PSV4 may include a same material as any one of the first to third passivation layers PSV1 to PSV3, but embodiments are not limited thereto.

[0241] On the fourth passivation layer PSV4, the first light conversion pattern CCP1 may be disposed in the second opening OP2.

[0242] The first light conversion pattern CCP1 may include color conversion particles and/or light

scattering particles. The color conversion particles may convert incident light into light of another color by changing a wavelength of the incident light. Also, the color conversion particles may scatter incident light. In embodiments, the color conversion particles may be quantum dots. The light scattering particles may scatter incident light.

[0243] The first sub-pixel SP1' may be a red sub-pixel. In case that the first light emitting element LD1' emits light of a blue color, the first light conversion pattern CCP1 may include first color conversion particles QD1 configured to convert light of the blue color into light of a red color. In case that the first light emitting element LD1' emits light of the red color, the first light conversion pattern CCP1 may include light scattering particles. As such, the particles included in the first light conversion pattern CCP1 may be variously changed according to the first light emitting element LD1'.

[0244] The low refractive layer LRL may be disposed on the second bank BNK2, the reflective layer RFL, and the first light conversion pattern CCP1. The low refractive layer LRL may have a refractive index lower than a refractive index of the first light conversion pattern CCP1. The low refractive layer LRL is configured to refract or totally reflect light according to an incident angle of the corresponding light. For example, the low refractive layer LRL may again provide light passing through the first light conversion pattern CCP1 to the first light conversion pattern CCP1.

Accordingly, the light conversion efficiency of the first light conversion pattern CCP1 can be improved.

[0245] The color filter layer CFL may be disposed on the low refractive layer LRL. The color filter layer CFL may include a first color filter CF1 and light blocking patterns LBP. The first color filter CF1 overlaps the first light conversion pattern CCP1. The first color filter CF1 may allow light in a desired wavelength range to be selectively transmitted therethrough. In case that the first sub-pixel SP1' is a red sub-pixel, the first color filter CF1 may include a red color filter. The light blocking patterns LBP may include at least one of various kinds of light blocking materials.

[0246] FIG. 14 is a sectional view taken along line X2-X2' shown in FIG. 12.

[0247] Referring to FIGS. 12 and 14, a pixel circuit layer PCL, a display panel layer DPL, and a light functional layer LFL may be provided on a substrate SUB.

[0248] The pixel circuit layer PCL and the display panel layer DPL are the same as described with reference to FIG. 13. In the pixel circuit layer PCL, sub-pixel circuits respectively corresponding to the first to third sub-pixels SP1', SP2', and SP3' are provided. In the display panel layer DPL, first to third light emitting elements LD1', LD2', and LD3' respectively corresponding to the first to third sub-pixels SP1', SP2', and SP3' may be provided. The first to third light emitting elements LD1', LD2', and LD3' may overlap first openings OP1 of a first bank BNK1. The first light emitting element LD1' may be connected between a cathode electrode CE' (see FIG. 13) and a transistor T_SP (see FIG. 13) included in a sub-pixel circuit of the first sub-pixel SP1'. The second light emitting element LD2' may be connected between the cathode electrode CE' and a transistor included in a sub-pixel circuit of the second sub-pixel SP2'. The third light emitting element LD3' may be connected between the cathode electrode CE' and a transistor included in a sub-pixel circuit of the third sub-pixel SP3'. Hereinafter, overlapping descriptions may be omitted.

[0249] The light functional layer LFL may be provided on the display panel layer DPL. The light functional layer LFL is the same as described with reference to FIG. 13. Hereinafter, overlapping descriptions may be omitted.

[0250] A second bank BNK2 may have second openings OP2. It may be understood that emission areas EMA and a non-emission area NEMA of the first to third sub-pixels SP1', SP2', and SP3' are defined by the second bank BNK2. An area overlapping the second bank BNK2 may correspond to the non-emission area NEMA. Areas overlapping the second openings OP2 of the second bank BNK2 may correspond to the emission areas EMA of the first to third sub-pixels SP1', SP2', and SP3'.

[0251] On a capping layer CPL, a fourth passivation layer PSV4 may be disposed in the second

openings OP2. On the fourth passivation layer PSV4, first and second light conversion patterns CCP1 and CCP2 and a light scattering pattern LSP may be disposed in the second openings OP2. [0252] In embodiments, the first to third light emitting elements LD1', LD2', and LD3' may be configured to emit light of a blue color. The first light conversion pattern CCP1 may include first color conversion particles QD1 configured to convert light of the blue color into light of a red color. The second light conversion pattern CCP2 may include second color conversion particles QD2 configured to convert light of the blue color into light of a green color. The light scattering pattern LSP may include light scattering particles SCT which scatter light of the blue color so as to improve light emission efficiency. Accordingly, the first to third sub-pixels SP1', SP2', and SP3' may be provided as a red sub-pixel, a green sub-pixel, and a blue sub-pixel, respectively. In embodiments, at least one of the first and second light conversion patterns CCP1 and CCP2 and the light scattering pattern LSP may further include color conversion patterns which convert light of the blue color into light of a white color.

[0253] In embodiments, the first to third light emitting elements LD1', LD2', and LD3' may be configured to emit lights of the red color, the green color, and the blue color, respectively. Each of the first and second light conversion patterns CCP1 and CCP2 and the light scattering pattern LSP may include the light scattering particles SCT. As such, the particles included in the first and second light conversion patterns CCP1 and CCP2 and the light scattering pattern LSP may be variously changed according to colors of lights emitted from the first to third light emitting elements LD1', LD2', and LD3'.

[0254] In embodiments, the first and second light conversion patterns CCP1 and CCP2 and the light scattering pattern LSP may be omitted.

[0255] A low refractive layer LRL may be disposed on the second bank BNK2, a reflective layer RFL, the first light conversion pattern CCP1, the second light conversion pattern CCP2, and the light scattering pattern LSP. The low refractive layer LRL may have a refractive index lower than a refractive index of each of the first and second light conversion patterns CCP1 and CCP2 and the light scattering pattern LSP. In embodiments, the low refractive layer LRL may be omitted in an area corresponding to the third sub-pixel SP3'.

[0256] A color filter layer CFL may be disposed on the low refractive layer LRL. The color filter layer CFL may include the first to third color filters CF1, CF2, and CF3 and light blocking patterns LBP.

[0257] Each of the first to third color filters CF1, CF2, and CF3 may allow light in a desired wavelength range to be selectively transmitted therethrough. In case that the first sub-pixel SP1' is a red sub-pixel, the first color filter CF1 may include a red color filter. In case that the second sub-pixel SP2' is a green sub-pixel, the second color filter CF2 may include a green color filter. In case that the third sub-pixel SP3' is a blue sub-pixel, the third color filter CF3 may include a blue color filter. The first to third color filters CF1, CF2, and CF3 may have a refractive index higher than the refractive index of the low refractive layer LRL. However, embodiments are not limited thereto, and the first to third color filters CF1, CF2, and CF3 may have a refractive index lower than or equal to the refractive index of the low refractive layer LRL.

[0258] The light blocking patterns LBP may be disposed between the color filters CF1, CF2, and CF3. It may be understood that the emission areas (or light output areas) EMA and the non-emission area NEMA of the first and second sub-pixels SP1', SP2', and SP3' are defined by the light blocking patterns LBP. An area overlapping the light blocking patterns LBP may correspond to the non-emission area NEMA. Areas not overlapping the light blocking patterns LBP may correspond to the emission areas EMA.

[0259] In embodiments, the light blocking patterns LBP may include at least one of various kinds of light blocking materials. In embodiments, each of the light blocking patterns LBP may be provided in the form of a multi-layer overlapping at least two color filters among the first to third color filters CF1, CF2, and CF3. For example, each of the light blocking patterns LBP may be

formed as the first to third color filters CF1, CF2, and CF3 overlap each other. In another example, a light blocking pattern between the first and second color filters CF1 and CF2 among the light blocking patterns LBP may be formed as a multi-layer in which the first and second color filters CF1 and CF2 overlap each other, and a light blocking pattern between the second and third color filters CF2 and CF3 among the light blocking patterns LBP may be formed as a multi-layer in which the second and third color filters CF2 and CF3 overlap each other. A light blocking pattern between the first color filter CF1 and a third color filter CF3 of an adjacent pixel may be formed as a multi-layer in which the first and third color filters CF1 and CF3 overlap each other. As such, each of the first to third color filters CF1, CF2, and CF3 may extend to the non-emission area NEMA to form the light blocking patterns LBP.

[0260] FIG. 15 is a block diagram illustrating a display system in accordance with an embodiment. [0261] Referring to FIG. 15, the display system 1000 may include a processor 1100 and a display device 1200.

[0262] The processor 1100 may perform various tasks and various calculations. In embodiments, the processor 1100 may include an Application Processor (AP), a Graphics Processing Unit (GPU), a microprocessor, a Central Processing Unit (CPU), and the like within the spirit and the scope of the disclosure. The processor 1100 may be connected to other components of the display system 1000 through a bus system to control the components of the display system 1000.

[0263] The processor 1100 may transmit image data IMG and a control signal CTRL to the display device 1200. The display device 1200 may display an image, based on the image data IMG and the control signal CTRL. The display device 1200 may be configured identical to the display device DD described with reference to FIG. 1. The image data IMG and the control signal CTRL may be provided as the input image data IMG and the control signal CTRL, which are shown in FIG. 1, respectively.

[0264] The display system 1000 may include a computing system for providing an image display function, such as a smart watch, a mobile phone, a smartphone, a portable computer, a tablet personal computer (PC), a watch phone, an automotive display, a smart glass, a portable multimedia player (PMP), a navigation system, or an ultra mobile computer (UMPC). The display system 1000 may include at least one of a head mounted display (HMD) device, a virtual reality (VR) device, a mixed reality (MR) device, and an augmented reality (AR) device.

[0265] FIGS. 16 to 19 are schematic perspective views illustrating application examples of the display system shown in FIG. 15.

[0266] Referring to FIG. 16, the display system 1000 shown in FIG. 15 may be applied to a smart watch 2000 including a display part 2100 and a strap part 2200.

[0267] The smart watch 2000 may be a wearable electronic device. For example, the smart watch 2000 may have a structure in which the strap part 2200 is mounted on a wrist of a user. The display system 1000 and/or the display device 1200 may be applied to the display part 2100, so that image data including time information can be provided to the user.

[0268] Referring to FIG. 17, the display system 1000 shown in FIG. 15 may be applied to an automotive display system 3000. The automotive display system 3000 may include a computing system provided at the inside/outside of a vehicle to provide image data.

[0269] For example, the display system 1000 and/or the display device 1200 may be applied to at least one of an infotainment panel 3100, a cluster 3200, a co-driver display 3300, a head-up display 3400, a side mirror display 3500, and a rear seat display 3600, which are provided in the vehicle.

[0270] Referring to FIG. 18, the display system 1000 shown in FIG. 15 may be applied to smart glasses 4000. The smart glasses 4000 are a wearable electronic device which can be worn on the face of a user. For example, the smart glasses 4000 may be a wearable device for Augmented Reality (AR).

[0271] The smart glasses 4000 may include a frame 4100 and a lens part 4200. The frame 4100 may include a housing 4110 supporting the lens part 4200 and a leg part 4120 for allowing the user

to wear the smart glasses **4000**. The leg part **4120** may be connected to the housing **4110** through a hinge, to be folded or unfolded with respect to the housing **4110**.

[0272] A battery, a touch pad, a microphone, a camera, and the like may be built in the frame **4100**. A projector for outputting light, a processor for controlling a light signal, and the like may be built in the frame **4100**.

[0273] The lens part **4200** may be an optical member which allows light to be transmitted therethrough or allows light to be reflected thereby. For example, the lens part **4200** may include glass, transparent synthetic resin, and the like within the spirit and the scope of the disclosure.

[0274] In order to enable eyes of the user to recognize visual information, the lens part **4200** may allow an image caused by a light signal transmitted from the projector of the frame **4100** to be reflected by a rear surface (for example, a surface in a direction facing the eyes of the user) of the lens part **4200**. For example, the user may recognize information including time, data, and the like, which are displayed on the lens part **4200**. The projector and/or the lens part **4200** may be a kind of display device. The display device **1200** may be applied to the projector and/or the lens part **4200**.

[0275] Referring to FIG. **19**, the display system **1000** shown in FIG. **15** may be applied to a head mounted display device **5000**.

[0276] The head mounted display device **5000** may be a wearable electronic device which can be worn on the head of a user. For example, the head mounted display device **5000** may be a wearable device for virtual reality (VR) or mixed reality (MR).

[0277] The head mounted display device **5000** may include a head mounted band **5100** and a display accommodating case **5200**. The head mounted band **5100** may be connected to the display accommodating case **5200**. The head mounted band **5100** may include a horizontal band and/or a vertical band, used to fix the head mounted display device **5000** to the head of the user. The horizontal band may be configured to surround a side portion of the head of the user, and the vertical band may be configured to surround an upper portion of the head of the user. However, embodiments are not limited thereto. For example, the head mounted band **5100** may be implemented in the form of a glasses frame, a helmet or the like within the spirit and the scope of the disclosure.

[0278] The display device accommodating case **5200** may accommodate the display system **1000** and/or the display device **1200**.

[0279] In the light emitting element in accordance with the disclosure, a second bonding electrode electrically connected to a second semiconductor layer may cover at least a portion of a bottom surface of a light emitting stack structure. Accordingly, a current density gradient in an active layer can become relatively more uniform. Thus, the lifetime and emission distribution uniformity of the light emitting element can be improved.

[0280] In the display device in accordance with the disclosure, the display device may include the light emitting element. For example, the display device may include the light emitting element provided as a lateral chip type light emitting element or a flip chip type light emitting element. Accordingly, the display quality of the display device can be improved.

[0281] Example embodiments have been disclosed herein, and although terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purpose of limitation. In some instances, as would be apparent to one of ordinary skill in the art, features, characteristics, and/or elements described in connection with a given embodiment may be used singly or in combination with features, characteristics, and/or elements described in connection with other embodiments unless otherwise indicated. Accordingly, it will be understood by those of skill in the art that various changes in form and details may be made without departing from the spirit and scope of the disclosure and as set forth in the following claims.

Claims

- 1.** A light emitting element comprising: a light emitting stack structure including a first semiconductor layer, a second semiconductor layer disposed below the first semiconductor layer, and an active layer disposed between the first semiconductor layer and the second semiconductor layer; a first bonding electrode disposed on the first semiconductor layer, the first bonding electrode electrically connected to the first semiconductor layer; and a second bonding electrode spaced apart from the first bonding electrode, the second bonding electrode electrically connected to the second semiconductor layer, wherein the second bonding electrode covers at least a portion of a bottom surface of the light emitting stack structure.
- 2.** The light emitting element of claim 1, wherein the second bonding electrode directly covers the entire bottom surface of the light emitting stack structure.
- 3.** The light emitting element of claim 1, wherein the second semiconductor layer includes: a first doping portion disposed below the active layer; and a second doping portion disposed below the first doping portion.
- 4.** The light emitting element of claim 3, wherein a first average doping concentration at the first doping portion is greater than a second average doping concentration at the second doping portion.
- 5.** The light emitting element of claim 3, wherein a thickness of the second doping portion is less than a thickness of the first doping portion.
- 6.** The light emitting element of claim 1, wherein the second semiconductor layer includes: a first portion disposed below the active layer and overlapping the active layer in a plan view; and a second portion disposed below the first portion, the second portion having an area larger than an area of the first portion in a plan view.
- 7.** The light emitting element of claim 6, wherein the second bonding electrode includes: a (2-1)th bonding electrode electrically connected to the second portion on the second portion not overlapping the first portion; and a (2-2)th bonding electrode electrically contacting the (2-1)th bonding electrode, the (2-2)th bonding electrode covering at least a portion of the bottom surface of the light emitting stack structure while extending along a side surface of the second portion.
- 8.** The light emitting element of claim 6, wherein the first semiconductor layer, the active layer, and the first portion overlap each other in a plan view.
- 9.** The light emitting element of claim 1, further comprising: an insulative film covering at least a portion of an outer circumferential surface of the light emitting stack structure.
- 10.** The light emitting element of claim 9, wherein the first bonding electrode is electrically connected to the first semiconductor layer through a first penetration hole defined in the insulative film, and the second bonding electrode is electrically connected to the second semiconductor layer through a second penetration hole defined in the insulative film.
- 11.** The light emitting element of claim 9, wherein the bottom surface of the light emitting stack structure is not covered by the insulative film.
- 12.** The light emitting element of claim 1, further comprising: an auxiliary electrode disposed between the first semiconductor layer and the first bonding electrode.
- 13.** The light emitting element of claim 12, wherein the first bonding electrode electrically contacts the auxiliary electrode.
- 14.** The light emitting element of claim 12, wherein the auxiliary electrode directly covers an entire top surface of the first semiconductor layer.
- 15.** A display device comprising: an anode electrode disposed on a pixel circuit layer; a cathode electrode disposed on the pixel circuit layer; and a light emitting element disposed on the anode electrode and the cathode electrode, wherein the light emitting element includes: a light emitting stack structure including a first semiconductor layer, a second semiconductor layer disposed below the first semiconductor layer, and an active layer disposed between the first semiconductor layer and the second semiconductor layer; a first bonding electrode disposed on the first semiconductor layer, the bonding electrode electrically connected to each of the first semiconductor layer and the

anode electrode; and a second bonding electrode spaced apart from the first bonding electrode, the second bonding electrode electrically connected to each of the second semiconductor layer and the cathode electrode, and the second bonding electrode covers at least a portion of a bottom surface of the light emitting stack structure.

16. The display device of claim 15, wherein the second bonding electrode directly covers the entire bottom surface of the light emitting stack structure.

17. The display device of claim 15, wherein a portion of the second bonding electrode, which covers the bottom surface of the light emitting stack structure, includes a metal material.

18. A display device comprising: an anode electrode disposed on a pixel circuit layer; a cathode electrode disposed on the pixel circuit layer; and a light emitting element disposed on the anode electrode and the cathode electrode, wherein the light emitting element includes: a light emitting stack structure including a first semiconductor layer, a second semiconductor layer disposed on the first semiconductor layer, and an active layer disposed between the first semiconductor layer and the second semiconductor layer; a first bonding electrode disposed below the first semiconductor layer, the first bonding electrode electrically connected to each of the first semiconductor layer and the anode electrode; and a second bonding electrode spaced apart from the first bonding electrode, the second bonding electrode electrically connected to each of the second semiconductor layer and the cathode electrode, and the second bonding electrode covers at least a portion of a top surface of the light emitting stack structure.

19. The display device of claim 18, wherein the second bonding electrode directly covers the entire top surface of the light emitting stack structure.

20. The display device of claim 18, wherein a portion of the second bonding electrode, which covers the top surface of the light emitting stack structure, includes a metal oxide.

21. An electronic device comprising: a processor to provide input image data; and a display device to display an image based on the input image data, wherein the display device includes: an anode electrode disposed on a pixel circuit layer; a cathode electrode disposed on the pixel circuit layer; and a light emitting element disposed on the anode electrode and the cathode electrode, wherein the light emitting element includes: a light emitting stack structure including a first semiconductor layer, a second semiconductor layer disposed below the first semiconductor layer, and an active layer disposed between the first semiconductor layer and the second semiconductor layer; a first bonding electrode disposed on the first semiconductor layer, the bonding electrode electrically connected to each of the first semiconductor layer and the anode electrode; and a second bonding electrode spaced apart from the first bonding electrode, the second bonding electrode electrically connected to each of the second semiconductor layer and the cathode electrode, and the second bonding electrode covers at least a portion of a bottom surface of the light emitting stack structure.
