

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12414284
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Yamazaki; Shunpei et al.

Semiconductor device and method for manufacturing semiconductor device

Abstract

A semiconductor device with a small variation in characteristics is provided. A semiconductor device includes an oxide, a first conductor and a second conductor over the oxide, a first insulator over the first conductor, a second insulator over the second conductor, a third insulator over the first insulator and the second insulator, a fourth insulator over the third insulator, a fifth insulator that is over the oxide and placed between the first conductor and the second conductor, a sixth insulator over the fifth insulator, and a third conductor over the sixth insulator. The third conductor includes a region overlapping the oxide. The fifth insulator includes a region in contact with the oxide, the first conductor, the second conductor, and each of the first insulator to the fourth insulator. The fifth insulator contains nitrogen, oxygen, and silicon.

Inventors:	Yamazaki; Shunpei (Tokyo, JP), Kakehata; Tetsuya (Kanagawa, JP), Jinbo; Yasuhiro (Kanagawa, JP), Egi; Yuji (Kanagawa, JP)
Applicant:	SEMICONDUCTOR ENERGY LABORATORY CO., LTD. (Atsugi, JP)
Family ID:	76575251
Assignee:	Semiconductor Energy Laboratory Co., Ltd. (Atsugi, JP)
Appl. No.:	17/786271
Filed (or PCT Filed):	December 15, 2020
PCT No.:	PCT/IB2020/061920
PCT Pub. No.:	WO2021/130600
PCT Pub. Date:	July 01, 2021

Prior Publication Data

Document Identifier	Publication Date
----------------------------	-------------------------

Foreign Application Priority Data

JP	2019-239444	Dec. 27, 2019
JP	2020-005762	Jan. 17, 2020

Publication Classification

Int. Cl.: H10B12/00 (20230101); H10D30/67 (20250101); H10D86/40 (20250101); H10D86/60 (20250101); H10D87/00 (20250101); H10D99/00 (20250101)

U.S. Cl.:

CPC H10B12/00 (20230201); H10D30/6734 (20250101); H10D30/6755 (20250101); H10D86/423 (20250101); H10D86/481 (20250101); H10D86/60 (20250101); H10D87/00 (20250101); H10D99/00 (20250101);

Field of Classification Search

USPC: None

References Cited**U.S. PATENT DOCUMENTS**

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8455868	12/2012	Yamazaki et al.	N/A	N/A
8547771	12/2012	Koyama	N/A	N/A
8796682	12/2013	Sasagawa et al.	N/A	N/A
8846459	12/2013	Tochibayashi et al.	N/A	N/A
8952377	12/2014	Yamazaki et al.	N/A	N/A
9431468	12/2015	Kawashima et al.	N/A	N/A
9698276	12/2016	Yamazaki	N/A	N/A
9859117	12/2017	Yamazaki	N/A	N/A
9947777	12/2017	Yamazaki et al.	N/A	N/A
9947801	12/2017	Yamazaki et al.	N/A	N/A
10032918	12/2017	Yamazaki et al.	N/A	N/A
10164120	12/2017	Kurata et al.	N/A	N/A
10236357	12/2018	Yamane et al.	N/A	N/A
10269559	12/2018	Abel et al.	N/A	N/A
10367014	12/2018	Yamazaki et al.	N/A	N/A
10505051	12/2018	Ito et al.	N/A	N/A
10658172	12/2019	Abel et al.	N/A	N/A
10741587	12/2019	Tochibayashi et al.	N/A	N/A
10871669	12/2019	Yamazaki et al.	N/A	N/A
10886412	12/2020	Yamazaki	N/A	N/A
11088286	12/2020	Hodo et al.	N/A	N/A
11152513	12/2020	Yamazaki et al.	N/A	N/A
11195758	12/2020	Yamazaki et al.	N/A	N/A

11316051	12/2021	Yamazaki et al.	N/A	N/A
2015/0287831	12/2014	Tanaka et al.	N/A	N/A
2016/0154268	12/2015	Yamazaki et al.	N/A	N/A
2017/0263651	12/2016	Tochibayashi et al.	N/A	N/A
2019/0080903	12/2018	Abel et al.	N/A	N/A
2019/0139783	12/2018	Yamazaki et al.	N/A	N/A
2020/0135445	12/2019	Yamazaki et al.	N/A	N/A
2020/0243685	12/2019	Yamazaki et al.	N/A	N/A
2021/0159342	12/2020	Asami	N/A	N/A
2021/0320193	12/2020	Yamazaki et al.	N/A	N/A
2022/0367450	12/2021	Yamazaki	N/A	H01L 29/792

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2011-151383	12/2010	JP	N/A
2012-257187	12/2011	JP	N/A
2017-168839	12/2016	JP	N/A
2019-087576	12/2018	JP	N/A
2020-535633	12/2019	JP	N/A
2020-0042542	12/2019	KR	N/A
201937571	12/2018	TW	N/A
WO-2019/055317	12/2018	WO	N/A
WO-2019/087715	12/2018	WO	N/A
WO-2019/171196	12/2018	WO	N/A
WO-2021/070007	12/2020	WO	N/A

OTHER PUBLICATIONS

International Search Report (Application No. PCT/IB2020/061920) Dated Mar. 23, 2021. cited by applicant

Written Opinion (Application No. PCT/IB2020/061920) Dated Mar. 23, 2021. cited by applicant
Murata.T et al., “Low-Temperature Silicon Oxide Offset Spacer Using Plasma-Enhanced Atomic Layer Deposition for High-k/Metal Gate Transistor”, Jpn. J. Appl. Phys. (Japanese Journal of Applied Physics) , Apr. 25, 2010, vol. 49, No. 4, pp. 04DB11-1-04DB11-5. cited by applicant

Taiwanese Office Action (Application No. 109145395) Dated May 27, 2024. cited by applicant

Primary Examiner: Lee; Kyoung

Attorney, Agent or Firm: Fish & Richardson P.C.

Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS

(1) This application is a U.S. National Phase Application under 35 U.S.C. § 371 of International Application PCT/IB2020/061920, filed on Dec. 15, 2020, which is incorporated by reference and claims the benefit of foreign priority applications filed in Japan on Dec. 27, 2019, as Application No. 2019-239444 and on Jan. 17, 2020, as Application No. 2020-005762.

TECHNICAL FIELD

(2) One embodiment of the present invention relates to a transistor, a semiconductor device, and an electronic device. Another embodiment of the present invention relates to a method for manufacturing a semiconductor device. Another embodiment of the present invention relates to a semiconductor wafer and a module.

(3) Note that in this specification and the like, a semiconductor device generally means a device that can function by utilizing semiconductor characteristics. A semiconductor element such as a transistor, a semiconductor circuit, an arithmetic device, and a storage device are each one embodiment of a semiconductor device. It can be sometimes said that a display device (a liquid crystal display device, a light-emitting display device, or the like), a projection device, a lighting device, an electro-optical device, a power storage device, a storage device, a semiconductor circuit, an imaging device, an electronic device, and the like include a semiconductor device.

(4) Note that one embodiment of the present invention is not limited to the above technical field. One embodiment of the invention disclosed in this specification and the like relates to an object, a method, or a manufacturing method. One embodiment of the present invention relates to a process, a machine, manufacture, or a composition of matter.

BACKGROUND ART

(5) In recent years, semiconductor devices have been developed to be mainly used for an LSI, a CPU, a memory, or the like. A CPU is an aggregation of semiconductor elements; the CPU includes a semiconductor integrated circuit (including at least a transistor and a memory) formed into a chip by processing a semiconductor wafer, and is provided with an electrode that is a connection terminal.

(6) A semiconductor circuit (IC chip) of an LSI, a CPU, a memory, or the like is mounted on a circuit board, for example, a printed wiring board, to be used as one of components of a variety of electronic devices.

(7) A technique by which a transistor is formed using a semiconductor thin film formed over a substrate having an insulating surface has been attracting attention. The transistor is used in a wide range of electronic devices such as an integrated circuit (IC) and an image display device (also simply referred to as a display device). A silicon-based semiconductor material is widely known as a semiconductor thin film applicable to the transistor; in addition, an oxide semiconductor has been attracting attention as another material.

(8) It is known that a transistor using an oxide semiconductor has an extremely low leakage current in a non-conduction state. For example, Patent Document 1 discloses a low-power-consumption CPU utilizing a feature of a low leakage current of the transistor using an oxide semiconductor. Furthermore, for example, Patent Document 2 discloses a storage device that can retain stored contents for a long time by utilizing a feature of a low leakage current of the transistor using an oxide semiconductor.

(9) In recent years, demand for an integrated circuit with higher density has risen with reductions in size and weight of electronic devices. Furthermore, the productivity of a semiconductor device including an integrated circuit is required to be improved.

REFERENCE

Patent Document

(10) [Patent Document 1] Japanese Published Patent Application No. 2012-257187 [Patent Document 2] Japanese Published Patent Application No. 2011-151383

SUMMARY OF THE INVENTION

Problems to be Solved by the Invention

(11) An object of one embodiment of the present invention is to provide a semiconductor device with a small variation in transistor characteristics. Another object of one embodiment of the present invention is to provide a semiconductor device with favorable reliability. Another object of one embodiment of the present invention is to provide a semiconductor device having favorable electrical characteristics. Another object of one embodiment of the present invention is to provide a

semiconductor device with a high on-state current. Another object of one embodiment of the present invention is to provide a semiconductor device that can be miniaturized or highly integrated. Another object of one embodiment of the present invention is to provide a semiconductor device with low power consumption.

(12) Note that the descriptions of these objects do not preclude the existence of other objects. One embodiment of the present invention does not have to achieve all these objects. Other objects are apparent from the descriptions of the specification, the drawings, the claims, and the like, and other objects can be derived from the descriptions of the specification, the drawings, the claims, and the like.

Means for Solving the Problems

(13) One embodiment of the present invention is a method for manufacturing a semiconductor device, including steps of depositing a first insulator, depositing an oxide film over the first insulator, performing first heat treatment, depositing a first conductive film and a first insulating film in this order over the oxide film, processing the oxide film, the first conductive film, and the first insulating film into island shapes to form an oxide, a conductive layer, and an insulating layer, depositing a second insulator over the first insulator, the oxide, the conductive layer, and the insulating layer, depositing a third insulator over the second insulator, forming an opening in the conductive layer, the insulating layer, the second insulator, and the third insulator to reach the oxide, forming a first conductor and a second conductor from the conductive layer and forming a fourth insulator and a fifth insulator from the insulating layer by the formation of the opening, performing second heat treatment, depositing a second insulating film over the third insulator and the opening, depositing a third insulating film over the second insulating film, performing microwave treatment, depositing a second conductive film over the third insulating film, and performing CMP treatment on the second insulating film, the third insulating film, and the second conductive film until a top surface of the third insulator is exposed to form a sixth insulator, a seventh insulator, and a third conductor; in which the second insulating film is deposited by a PEALD method using a gas containing silicon but not containing hydrocarbon and an oxidizing gas.

(14) In the above, it is preferable that the deposition by the PEALD method include a first step of introducing the gas containing silicon but not containing hydrocarbon and the oxidizing gas into a reaction chamber, a second step of stopping the introduction of the gas containing silicon but not containing hydrocarbon and purging the gas containing silicon but not containing hydrocarbon remaining in the reaction chamber, a third step of applying high-frequency power to generate plasma due to the oxidizing gas, and a fourth step of stopping the application of the high-frequency power; the first step to the fourth step be regarded as one cycle; and one cycle to 500 cycles be performed.

(15) In the above, it is preferable that the gas containing silicon but not containing hydrocarbon contain any one or more selected from SiH_4 , Si_2H_6 , SiF_4 , SiCl_4 , SiBr_4 , SiH_2Cl_2 , and SiH_2I_2 , and the oxidizing gas contain any one or more selected from O_2 , O_3 , N_2O , NO_2 , and H_2O .

(16) In the above, it is preferable that the gas containing silicon but not containing hydrocarbon be SiH_4 and the oxidizing gas be N_2O .

(17) In the above, the pressure in the reaction chamber in the first step is preferably higher than or equal to 400 Pa and lower than or equal to 1000 Pa.

(18) In the above, the temperature of the first heat treatment is preferably higher than the temperature of the second heat treatment.

(19) Another embodiment of the present invention is a semiconductor device including an oxide, a first conductor and a second conductor over the oxide, a first insulator over the first conductor, a second insulator over the second conductor, a third insulator over the first insulator and the second insulator, a fourth insulator over the third insulator, a fifth insulator that is over the oxide and

placed between the first conductor and the second conductor, a sixth insulator over the fifth insulator, and a third conductor over the sixth insulator; the third conductor includes a region overlapping the oxide; the fifth insulator comprises a region in contact with the oxide, the first conductor, the second conductor, and each of the first insulator to the fourth insulator; and the fifth insulator contains nitrogen, oxygen, and silicon.

(20) In the above, the sixth insulator preferably contains hafnium.

(21) In the above, a thickness of the sixth insulator is preferably greater than or equal to 0.5 nm and less than or equal to 5.0 nm.

(22) In the above, a thickness of the fifth insulator is preferably greater than or equal to 0.5 nm and less than or equal to 15.0 nm.

(23) In the above, the oxide is preferably an oxide semiconductor containing any one or more selected from In, Ga, and Zn.

Effect of the Invention

(24) According to one embodiment of the present invention, a semiconductor device with a small variation in transistor characteristics can be provided. According to another embodiment of the present invention, a semiconductor device with favorable reliability can be provided. According to another embodiment of the present invention, a semiconductor device having favorable electrical characteristics can be provided. According to another embodiment of the present invention, a semiconductor device with a high on-state current can be provided. According to another embodiment of the present invention, a semiconductor device that can be miniaturized or highly integrated can be provided. According to another embodiment of the present invention, a semiconductor device with low power consumption can be provided.

(25) Note that the descriptions of these effects do not preclude the existence of other effects. One embodiment of the present invention does not have to have all these effects. Other effects are apparent from the descriptions of the specification, the drawings, the claims, and the like, and other effects can be derived from the descriptions of the specification, the drawings, the claims, and the like.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1A is a top view of a semiconductor device of one embodiment of the present invention.

(2) FIG. 1B to FIG. 1D are cross-sectional views of the semiconductor device of one embodiment of the present invention.

(3) FIG. 2A is a top view of a semiconductor device of one embodiment of the present invention.

(4) FIG. 2B to FIG. 2D are cross-sectional views of the semiconductor device of one embodiment of the present invention.

(5) FIG. 3 is a cross-sectional view of a semiconductor device of one embodiment of the present invention.

(6) FIG. 4A is a diagram showing the classification of crystal structures of IGZO. FIG. 4B is a diagram showing an XRD spectrum of a CAAC-IGZO film. FIG. 4C is a diagram showing a nanobeam electron diffraction pattern of a CAAC-IGZO film.

(7) FIG. 5 is a flow chart showing a process of one embodiment of the present invention.

(8) FIG. 6A and FIG. 6B are diagrams showing deposition sequences of one embodiment of the present invention.

(9) FIG. 7A is a top view illustrating a method for manufacturing a semiconductor device of one embodiment of the present invention. FIG. 7B to FIG. 7D are cross-sectional views illustrating the method for manufacturing the semiconductor device of one embodiment of the present invention.

(10) FIG. 8A is a top view illustrating the method for manufacturing the semiconductor device of

present invention.

(23) FIG. 21A is a top view illustrating the method for manufacturing the semiconductor device of one embodiment of the present invention. FIG. 21B to FIG. 21D are cross-sectional views illustrating the method for manufacturing the semiconductor device of one embodiment of the present invention.

(24) FIG. 22A is a top view illustrating the method for manufacturing the semiconductor device of one embodiment of the present invention. FIG. 22B to FIG. 22D are cross-sectional views illustrating the method for manufacturing the semiconductor device of one embodiment of the present invention.

(25) FIG. 23 is a top view illustrating a microwave treatment apparatus of one embodiment of the present invention.

(26) FIG. 24 is a cross-sectional view illustrating the microwave treatment apparatus of one embodiment of the present invention.

(27) FIG. 25 is a cross-sectional view illustrating the microwave treatment apparatus of one embodiment of the present invention.

(28) FIG. 26 is a cross-sectional view illustrating a microwave treatment apparatus of one embodiment of the present invention.

(29) FIG. 27A and FIG. 27B are cross-sectional views of semiconductor devices of one embodiment of the present invention.

(30) FIG. 28 is a cross-sectional view illustrating a structure of a storage device of one embodiment of the present invention.

(31) FIG. 29 is a cross-sectional view illustrating a structure of a storage device of one embodiment of the present invention.

(32) FIG. 30A is a cross-sectional view of a semiconductor device of one embodiment of the present invention. FIG. 30B is a cross-sectional view of a semiconductor device of one embodiment of the present invention.

(33) FIG. 31A is a cross-sectional view of a semiconductor device of one embodiment of the present invention. FIG. 31B is a cross-sectional view of a semiconductor device of one embodiment of the present invention.

(34) FIG. 32 is a cross-sectional view of a semiconductor device of one embodiment of the present invention.

(35) FIG. 33 is a cross-sectional view of a semiconductor device of one embodiment of the present invention.

(36) FIG. 34A and FIG. 34B are block diagrams of a structure example of a storage device of one embodiment of the present invention.

(37) FIG. 35A to FIG. 35H are circuit diagrams of structure examples of storage devices of one embodiment of the present invention.

(38) FIG. 36A and FIG. 36B are schematic views of semiconductor devices of one embodiment of the present invention.

(39) FIG. 37A and FIG. 37B are diagrams illustrating examples of electronic components of an embodiment of the present invention.

(40) FIG. 38A to FIG. 38E are schematic views of storage devices of one embodiment of the present invention.

(41) FIG. 39A to FIG. 39H are diagrams illustrating electronic devices of one embodiment of the present invention.

(42) FIG. 40 is a diagram showing an ALD Window of this example.

(43) FIG. 41 is a diagram in which GPC at each substrate temperature of this example is plotted.

(44) FIG. 42A is a STEM cross-sectional image of this example. FIG. 42B is a diagram showing thickness measurement results.

MODE FOR CARRYING OUT THE INVENTION

(45) Hereinafter, embodiments are described with reference to the drawings. Note that the embodiments can be implemented with many different modes, and it is readily understood by those skilled in the art that modes and details thereof can be changed in various ways without departing from the spirit and scope thereof. Thus, the present invention should not be interpreted as being limited to the description of the embodiments below.

(46) In the drawings, the size, the layer thickness, or the region is exaggerated for clarity in some cases. Therefore, they are not limited to the illustrated scale. Note that the drawings schematically illustrate ideal examples, and embodiments of the present invention are not limited to shapes, values, and the like shown in the drawings. For example, in the actual manufacturing process, a layer, a resist mask, or the like might be unintentionally reduced in size by treatment such as etching, which might not be reflected in the drawings for easy understanding. Furthermore, in the drawings, the same reference numerals are used in common for the same portions or portions having similar functions in different drawings, and repeated description thereof is omitted in some cases. Furthermore, the same hatch pattern is used for the portions having similar functions, and the portions are not especially denoted by reference numerals in some cases.

(47) Furthermore, especially in a top view (also referred to as a “plan view”), a perspective view, or the like, the description of some components might be omitted for easy understanding of the invention. In addition, some hidden lines and the like might not be illustrated.

(48) The ordinal numbers such as “first” and “second” in this specification and the like are used for convenience and do not denote the order of steps or the stacking order of layers. Therefore, for example, the term “first” can be replaced with the term “second”, “third”, or the like as appropriate. In addition, the ordinal numbers in this specification and the like do not sometimes correspond to the ordinal numbers that are used to specify one embodiment of the present invention.

(49) Moreover, in this specification and the like, terms for describing arrangement, such as “over” and “under”, are used for convenience for describing the positional relation between components with reference to drawings. The positional relationship between components is changed as appropriate in accordance with a direction in which the components are described. Thus, without limitation to terms described in this specification, the description can be changed appropriately depending on the situation.

(50) When this specification and the like explicitly state that X and Y are connected, for example, the case where X and Y are electrically connected, the case where X and Y are functionally connected, and the case where X and Y are directly connected are regarded as being disclosed in this specification and the like. Accordingly, without being limited to a predetermined connection relationship, for example, a connection relationship shown in drawings or texts, a connection relationship other than one shown in drawings or texts is regarded as being disclosed in the drawings or the texts. Here, X and Y each denote an object (e.g., a device, an element, a circuit, a wiring, an electrode, a terminal, a conductive film, or a layer).

(51) In this specification and the like, a transistor is an element having at least three terminals including a gate, a drain, and a source. In addition, the transistor includes a region where a channel is formed (hereinafter also referred to as a channel formation region) between the drain (a drain terminal, a drain region, or a drain electrode) and the source (a source terminal, a source region, or a source electrode), and current can flow between the source and the drain through the channel formation region. Note that in this specification and the like, a channel formation region refers to a region through which a current mainly flows.

(52) Furthermore, functions of a source and a drain are sometimes interchanged with each other when transistors having different polarities are used or when the direction of current is changed in circuit operation, for example. Therefore, the terms “source” and “drain” can sometimes be interchanged with each other in this specification and the like.

(53) Note that a channel length refers to, for example, a distance between a source (a source region or a source electrode) and a drain (a drain region or a drain electrode) in a region where a

semiconductor (or a portion where current flows in a semiconductor when a transistor is in an on state) and a gate electrode overlap each other or a channel formation region in a top view of the transistor. Note that in one transistor, channel lengths in all regions do not necessarily have the same value. In other words, the channel length of one transistor is not fixed to one value in some cases. Thus, in this specification, the channel length is any one of the values, the maximum value, the minimum value, or the average value in a channel formation region.

(54) A channel width refers to, for example, the length of a channel formation region in a direction perpendicular to a channel length direction in a region where a semiconductor (or a portion where current flows in a semiconductor when a transistor is in an on state) and a gate electrode overlap each other, or a channel formation region in a top view of the transistor. Note that in one transistor, channel widths in all regions do not necessarily have the same value. In other words, the channel width of one transistor is not fixed to one value in some cases. Thus, in this specification, the channel width is any one of the values, the maximum value, the minimum value, or the average value in a channel formation region.

(55) Note that in this specification and the like, depending on the transistor structure, a channel width in a region where a channel is actually formed (hereinafter also referred to as an “effective channel width”) is sometimes different from a channel width shown in a top view of a transistor (hereinafter also referred to as an “apparent channel width”). For example, in a transistor whose gate electrode covers a side surface of a semiconductor, the effective channel width is larger than the apparent channel width, and its influence cannot be ignored in some cases.

(56) For example, in a miniaturized transistor whose gate electrode covers a side surface of a semiconductor, the proportion of a channel formation region formed in the side surface of the semiconductor is increased in some cases. In that case, the effective channel width is larger than the apparent channel width.

(57) In such a case, the effective channel width is sometimes difficult to estimate by actual measurement. For example, estimation of an effective channel width from a design value requires assumption that the shape of a semiconductor is known. Accordingly, in the case where the shape of a semiconductor is not known accurately, it is difficult to measure the effective channel width accurately.

(58) In this specification, the simple term “channel width” refers to an apparent channel width in some cases. Alternatively, in this specification, the simple term “channel width” refers to an effective channel width in some cases. Note that values of a channel length, a channel width, an effective channel width, an apparent channel width, and the like can be determined, for example, by analyzing a cross-sectional TEM image and the like.

(59) Note that impurities in a semiconductor refer to, for example, elements other than the main components of a semiconductor. For example, an element with a concentration lower than 0.1 atomic % can be regarded as an impurity. When an impurity is contained, for example, the density of defect states in a semiconductor increases and the crystallinity decreases in some cases. In the case where the semiconductor is an oxide semiconductor, examples of an impurity which changes the characteristics of the semiconductor include Group 1 elements, Group 2 elements, Group 13 elements, Group 14 elements, Group 15 elements, and transition metals other than the main components of the oxide semiconductor; hydrogen, lithium, sodium, silicon, boron, phosphorus, carbon, and nitrogen are given as examples. Note that water also serves as an impurity in some cases. In addition, oxygen vacancies (also referred to as V_{sub}.O) are formed in an oxide semiconductor in some cases by entry of impurities, for example.

(60) Note that in this specification and the like, silicon oxynitride is a material that contains more oxygen than nitrogen in its composition. Moreover, silicon nitride oxide is a material that contains more nitrogen than oxygen in its composition. Similarly, aluminum oxynitride refers to a material that contains more oxygen than nitrogen in its composition. Moreover, aluminum nitride oxide refers to a material that contains more nitrogen than oxygen in its composition. Similarly, hafnium

oxynitride refers to a material that contains more oxygen than nitrogen in its composition. Moreover, a hafnium nitride oxide is a material that contains more nitrogen than oxygen in its composition.

(61) In this specification and the like, the term “insulator” can be replaced with an insulating film or an insulating layer. Furthermore, the term “conductor” can be replaced with a conductive film or a conductive layer. Moreover, the term “semiconductor” can be replaced with a semiconductor film or a semiconductor layer.

(62) In this specification and the like, “parallel” indicates a state where two straight lines are placed at an angle greater than or equal to -10° and less than or equal to 10° . Accordingly, the case where the angle is greater than or equal to -5° and less than or equal to 5° is also included. Furthermore, “substantially parallel” indicates a state where two straight lines are placed at an angle greater than or equal to -30° and less than or equal to 30° . Moreover, “perpendicular” indicates a state where two straight lines are placed at an angle greater than or equal to 80° and less than or equal to 100° . Accordingly, the case where the angle is greater than or equal to 85° and less than or equal to 95° is also included. Furthermore, “substantially perpendicular” indicates a state where two straight lines are placed at an angle greater than or equal to 60° and less than or equal to 120° .

(63) In this specification and the like, a metal oxide is an oxide of a metal in a broad sense. Metal oxides are classified into an oxide insulator, an oxide conductor (including a transparent oxide conductor), an oxide semiconductor (also simply referred to as an OS), and the like. For example, in the case where a metal oxide is used in a semiconductor layer of a transistor, the metal oxide is referred to as an oxide semiconductor in some cases. That is, an OS transistor can also be called a transistor including a metal oxide or an oxide semiconductor.

(64) In this specification and the like, “normally off” means that a drain current per micrometer of channel width flowing through a transistor when no potential is applied to a gate or the gate is supplied with a ground potential is 1×10^{-20} A or lower at room temperature, 1×10^{-18} A or lower at 85°C ., or 1×10^{-16} A or lower at 125°C .

Embodiment 1

(65) In this embodiment, an example of a semiconductor device including a transistor **200** of one embodiment of the present invention and a manufacturing method thereof are described with reference to FIG. 1A to FIG. 22D.

(66) <Structure Example of Semiconductor Device>

(67) A structure of a semiconductor device including the transistor **200** is described with reference to FIG. 1A to FIG. 1D. FIG. 1A to FIG. 1D are a top view and cross-sectional views of the semiconductor device including the transistor **200**. FIG. 1A is a top view of the semiconductor device. FIG. 1B to FIG. 1D are cross-sectional views of the semiconductor device. Here, FIG. 1B is a cross-sectional view of a portion indicated by dashed-dotted line A1-A2 in FIG. 1A, and is a cross-sectional view of the transistor **200** in the channel length direction. FIG. 1C is a cross-sectional view of a portion indicated by dashed-dotted line A3-A4 in FIG. 1A, and is a cross-sectional view of the transistor **200** in the channel width direction. FIG. 1D is a cross-sectional view of a portion indicated by dashed-dotted line A5-A6 in FIG. 1A. Note that for clarity of the drawing, some components are omitted in the top view of FIG. 1A.

(68) The semiconductor device of one embodiment of the present invention includes an insulator **212** over a substrate (not illustrated), an insulator **214** over the insulator **212**, the transistor **200** over the insulator **214**, an insulator **280** over the transistor **200**, an insulator **282** over the insulator **280** (an insulator **282a** and an insulator **282b**), an insulator **283** over the insulator **282**, an insulator **274** over the insulator **283**, an insulator **284** over the insulator **283** and the insulator **274**, and an insulator **286** over the insulator **284**. The insulator **212**, the insulator **214**, the insulator **280**, the insulator **282**, the insulator **283**, the insulator **284**, and the insulator **274** function as interlayer films. A conductor **240** (a conductor **240a** and a conductor **240b**) that is electrically connected to the transistor **200** and functions as a plug is also included. Note that an insulator **241** (an insulator **241a**

and an insulator **241b**) is provided in contact with side surfaces of the conductor **240** functioning as a plug. A conductor **246** (a conductor **246a** and a conductor **246b**) that is electrically connected to the conductor **240** and functions as a wiring is provided over the insulator **284** and the conductor **240**. The insulator **286** is provided over the conductor **246** and the insulator **284**.

(69) The insulator **283** is in contact with part of a top surface of the insulator **214**, a side surface of an insulator **216**, a side surface of an insulator **222**, a side surface of an insulator **272**, a side surface of the insulator **280**, and a side surface of the insulator **282**.

(70) The insulator **241a** is provided in contact with the inner wall of an opening in the insulator **280**, the insulator **282**, the insulator **283**, and the insulator **284**; a first conductor of the conductor **240a** is provided in contact with a side surface of the insulator **241a**; and a second conductor of the conductor **240a** is provided on the inner side thereof. The insulator **241b** is provided in contact with the inner wall of an opening in the insulator **280**, the insulator **282**, the insulator **283**, and the insulator **284**; a first conductor of the conductor **240b** is provided in contact with a side surface of the insulator **241b**; and a second conductor of the conductor **240b** is provided on the inner side thereof. Here, the level of a top surface of the conductor **240** and the level of a top surface of the insulator **284** in a region overlapping the conductor **246** can be substantially the same. Note that although the transistor **200** is illustrated to have a structure in which the first conductor of the conductor **240** and the second conductor of the conductor **240** are stacked, the present invention is not limited thereto. For example, the conductor **240** may be provided as a single layer or to have a stacked-layer structure of three or more layers. In the case where a component has a stacked-layer structure, layers may be distinguished by ordinal numbers corresponding to the formation order.

(71) [Transistor **200**]

(72) As illustrated in FIG. 1A to FIG. 1D, the transistor **200** includes the insulator **216** over the insulator **214**; a conductor **205** (a conductor **205a**, a conductor **205b**, and a conductor **205c**) placed to be embedded in the insulator **214** and/or the insulator **216**; the insulator **222** over the insulator **216** and the conductor **205**; an insulator **224** over the insulator **222**; an oxide **230a** over the insulator **224**; an oxide **230b** over the oxide **230a**; an oxide **243** (an oxide **243a** and an oxide **243b**) over the oxide **230b**; a conductor **242a** over the oxide **243a**; an insulator **271a** over the conductor **242a**; a conductor **242b** over the oxide **243b**; an insulator **271b** over the conductor **242b**; an insulator **250a** over the oxide **230b**; an insulator **250b** over the insulator **250a**, a conductor **260** (a conductor **260a** and a conductor **260b**) that is placed over the insulator **250b** and overlaps part of the oxide **230b**; the insulator **272** placed over the insulator **222**, the insulator **224**, the oxide **230** (the oxide **230a** and the oxide **230b**), the oxide **243**, the conductor **242** (the conductor **242a** and the conductor **242b**), and the insulator **271** (the insulator **271a** and the insulator **271b**). Here, as illustrated in FIG. 1B and FIG. 1C, a top surface of the conductor **260** is positioned to be substantially aligned with a top surface of the insulator **250** and a top surface of the insulator **280**. The insulator **282** is in contact with the top surfaces of the conductor **260**, the insulator **250**, and the insulator **280**.

(73) Hereinafter, the oxide **230a** and the oxide **230b** are collectively referred to as an oxide **230** in some cases. The insulator **250a** and the insulator **250b** are collectively referred to as an insulator **250** in some cases. The insulator **271a** and the insulator **271b** are collectively referred to as an insulator **271** in some cases.

(74) An opening reaching the oxide **230b** is provided in the insulator **280** and the insulator **272**. The insulator **250** and the conductor **260** are placed in the opening. In addition, in the channel length direction of the transistor **200**, the conductor **260** and the insulator **250** are provided between the insulator **271a**, the conductor **242a**, and the oxide **243a** and the insulator **271b**, the conductor **242b**, and the oxide **243b**. The insulator **250** includes a region in contact with a side surface of the conductor **260** and a region in contact with a bottom surface of the conductor **260**.

(75) The oxide **230** preferably includes the oxide **230a** placed over the insulator **224** and the oxide **230b** placed over the oxide **230a**. Including the oxide **230a** under the oxide **230b** makes it possible

to inhibit diffusion of impurities into the oxide **230b** from components formed below the oxide **230a**.

(76) Although a structure in which the oxide **230a** and the oxide **230b** are stacked as the oxide **230** in the transistor **200** is described, the present invention is not limited thereto. For example, the oxide **230** may be provided as a single layer of the oxide **230b** or to have a stacked-layer structure of three or more layers, or the oxide **230a** and the oxide **230b** may each have a stacked-layer structure.

(77) The conductor **260** functions as a first gate (also referred to as a top gate) electrode, and the conductor **205** functions as a second gate (also referred to as a back gate) electrode. The insulator **250** functions as a first gate insulator, and the insulator **222** and the insulator **224** function as a second gate insulator. The conductor **242a** functions as one of a source and a drain, and the conductor **242b** functions as the other of the source and the drain. A region of the oxide **230** that is overlapped by the conductor **260** functions as a channel formation region at least partly.

(78) Here, FIG. 3 is an enlarged view of the vicinity of the channel formation region in FIG. 1B. As illustrated in FIG. 3, the oxide **230b** includes a region **230bc** functioning as the channel formation region of the transistor **200** and a region **230ba** and a region **230bb** that are provided to sandwich the region **230bc** and function as a source region and a drain region. At least part of the region **230bc** is overlapped by the conductor **260**. In other words, the region **230bc** is provided in a region between the conductor **242a** and the conductor **242b**. The region **230ba** is provided to be overlapped by the conductor **242a**, and the region **230bb** is provided to be overlapped by the conductor **242b**.

(79) The region **230bc** functioning as the channel formation region is a high-resistance region with a low carrier concentration because it includes a smaller amount of oxygen vacancies or has a lower impurity concentration than the region **230ba** and the region **230bb**. The region **230ba** and the region **230bb** functioning as the source region and the drain region are each a low-resistance region with an increased carrier concentration because it includes a large amount of oxygen vacancies or has a high concentration of an impurity such as hydrogen, nitrogen, or a metal element. In other words, the region **230ba** and the region **230bb** are each a region having a higher carrier concentration and a lower resistance than the region **230bc**.

(80) The carrier concentration in the region **230bc** functioning as the channel formation region is preferably lower than or equal to $1 \times 10^{18} \text{ cm}^{-3}$, further preferably lower than $1 \times 10^{17} \text{ cm}^{-3}$, still further preferably lower than $1 \times 10^{16} \text{ cm}^{-3}$, yet further preferably lower than $1 \times 10^{13} \text{ cm}^{-3}$, yet still further preferably lower than $1 \times 10^{12} \text{ cm}^{-3}$. Note that the lower limit of the carrier concentration in the region **230bc** functioning as the channel formation region is not particularly limited and can be, for example, $1 \times 10^{-9} \text{ cm}^{-3}$.

(81) Between the region **230bc** and the region **230ba** or the region **230bb**, a region having a carrier concentration that is lower than or substantially equal to the carrier concentrations in the region **230ba** and the region **230bb** and higher than or substantially equal to the carrier concentration in the region **230bc** may be formed. That is, the region functions as a junction region between the region **230bc** and the region **230ba** or the region **230bb**. The hydrogen concentration in the junction region is sometimes lower than or substantially equal to the hydrogen concentrations in the region **230ba** and the region **230bb** and higher than or substantially equal to the hydrogen concentration in the region **230bc**. The amount of oxygen vacancies in the junction region is sometimes smaller than or substantially equal to the amounts of oxygen vacancies in the region **230ba** and the region **230bb** and larger than or substantially equal to the amount of oxygen vacancies in the region **230bc**.

(82) Although FIG. 3 illustrates an example in which the region **230ba**, the region **230bb**, and the region **230bc** are formed in the oxide **230b**, the present invention is not limited thereto. For example, the above regions may be formed not only in the oxide **230b** but also in the oxide **230a**.

(83) In the oxide **230**, the boundaries between the regions are difficult to detect clearly in some

cases. The concentration of a metal element and an impurity element such as hydrogen or nitrogen, which is detected in each region, may be gradually changed not only between the regions but also in each region. That is, the region closer to the channel formation region preferably has a lower concentration of a metal element and an impurity element such as hydrogen or nitrogen.

(84) In the transistor **200**, a metal oxide functioning as a semiconductor (such a metal oxide is hereinafter also referred to as an oxide semiconductor) is preferably used for the oxide **230** (the oxide **230a** and the oxide **230b**) including the channel formation region.

(85) The metal oxide functioning as a semiconductor preferably has a band gap of 2 eV or more, preferably 2.5 eV or more. With the use of a metal oxide having such a large band gap, the off-state current of the transistor can be reduced.

(86) As the oxide **230**, it is preferable to use, for example, a metal oxide such as an In-M-Zn oxide containing indium, an element M, and zinc (the element M is one or more kinds selected from aluminum, gallium, yttrium, tin, copper, vanadium, beryllium, boron, titanium, iron, nickel, germanium, zirconium, molybdenum, lanthanum, cerium, neodymium, hafnium, tantalum, tungsten, magnesium, and the like). Alternatively, an In—Ga oxide, an In—Zn oxide, or an indium oxide may be used as the oxide **230**.

(87) The atomic ratio of In to the element M in the metal oxide used as the oxide **230b** is preferably greater than the atomic ratio of In to the element M in the metal oxide used as the oxide **230a**.

(88) The oxide **230a** is placed under the oxide **230b**, whereby impurities and oxygen can be inhibited from diffusing into the oxide **230b** from components formed below the oxide **230a**.

(89) When the oxide **230a** and the oxide **230b** contain a common element (as the main component) besides oxygen, the density of defect states at an interface between the oxide **230a** and the oxide **230b** can be made low. Since the density of defect states at the interface between the oxide **230a** and the oxide **230b** can be made low, the influence of interface scattering on carrier conduction is small, and a high on-state current can be obtained.

(90) The oxide **230b** preferably has crystallinity. It is particularly preferable to use a CAAC-OS (c-axis aligned crystalline oxide semiconductor) as the oxide **230b**.

(91) The CAAC-OS is a metal oxide having a dense structure with high crystallinity and a small amount of impurities or defects (e.g., oxygen vacancies (V_{sub}.O)). In particular, after the formation of a metal oxide, heat treatment is performed at a temperature at which the metal oxide does not become a polycrystal (e.g., 400° C. to 600° C.), whereby a CAAC-OS having a dense structure with higher crystallinity can be obtained. When the density of the CAAC-OS is increased in such a manner, diffusion of impurities or oxygen in the CAAC-OS can be further reduced.

(92) On the other hand, a clear crystal grain boundary is difficult to observe in the CAAC-OS; thus, it can be said that a reduction in electron mobility due to the crystal grain boundary is less likely to occur. Thus, a metal oxide including a CAAC-OS is physically stable. Therefore, the metal oxide including a CAAC-OS is resistant to heat and has high reliability.

(93) If impurities and oxygen vacancies exist in a region of an oxide semiconductor where a channel is formed, a transistor using the oxide semiconductor might have variable electrical characteristics and poor reliability. In some cases, hydrogen in the vicinity of an oxygen vacancy forms a defect that is the oxygen vacancy into which hydrogen enters (hereinafter sometimes referred to as V_{sub}.OH), which generates an electron serving as a carrier. Therefore, when the region of the oxide semiconductor where a channel is formed includes oxygen vacancies, the transistor tends to have normally-on characteristics (characteristics with which, even when no voltage is applied to the gate electrode, the channel exists and current flows through the transistor). Thus, impurities, oxygen vacancies, and V_{sub}.OH are preferably reduced as much as possible in the region of the oxide semiconductor where a channel is formed. In other words, it is preferable that the region of the oxide semiconductor where a channel is formed have a reduced carrier concentration and be of an i-type (intrinsic) or substantially i-type.

(94) As a countermeasure to the above, an insulator containing oxygen that is released by heating

(hereinafter, sometimes referred to as excess oxygen) is provided in the vicinity of the oxide semiconductor so that oxygen can be supplied from the insulator to the oxide semiconductor to reduce oxygen vacancies and $V_{\text{sub.OH}}$ when heat treatment is performed. However, supply of an excess amount of oxygen to the source region or the drain region might cause a decrease in the on-state current or field-effect mobility of the transistor **200**. Furthermore, a variation in the amount of oxygen supplied to the source region or the drain region on the substrate plane leads to variable characteristics of the semiconductor device including the transistor.

(95) Therefore, the region **230bc** functioning as the channel formation region in the oxide semiconductor is preferably an i-type or substantially i-type region with reduced carrier concentration, whereas the region **230ba** and the region **230bb** functioning as the source region and the drain region are preferably n-type regions with high carrier concentrations. That is, it is preferable that oxygen vacancies and $V_{\text{sub.OH}}$ in the region **230bc** of the oxide semiconductor be reduced and the region **230ba** and the region **230bb** not be supplied with an excess amount of oxygen.

(96) Thus, in this embodiment, microwave treatment is performed in an oxygen-containing atmosphere in a state where the conductor **242a** and the conductor **242b** are provided over the oxide **230b** so that oxygen vacancies and $V_{\text{sub.OH}}$ in the region **230bc** are reduced. Here, the microwave treatment refers to, for example, treatment using an apparatus including a power source that generates high-density plasma with the use of a microwave.

(97) The microwave treatment in an oxygen-containing atmosphere converts an oxygen gas into plasma using a high-frequency wave such as a microwave or RF (Radio Frequency) and activates the oxygen plasma. At this time, the region **230bc** can be irradiated with the high-frequency wave such as the microwave or RF. By the effect of the plasma, the microwave, or the like, $V_{\text{sub.OH}}$ in the region **230bc** can be cut; thus, hydrogen (H) can be removed from the region **230bc** and an oxygen vacancy ($V_{\text{sub.O}}$) can be filled with oxygen. That is, the reaction " $V_{\text{sub.OH}} \rightarrow H + V_{\text{sub.O}}$ " occurs in the region **230bc**, so that the hydrogen concentration in the region **230bc** can be reduced. As a result, oxygen vacancies and $V_{\text{sub.OH}}$ in the region **230bc** can be reduced to lower the carrier concentration.

(98) In the microwave treatment in an oxygen-containing atmosphere, the high-frequency wave such as the microwave or RF, the oxygen plasma, or the like is blocked by the conductor **242a** and the conductor **242b** and does not affect the region **230ba** and the region **230bb**. In addition, the effect of the oxygen plasma can be reduced by the insulator **271** and the insulator **280** that are provided to cover the oxide **230b** and the conductor **242**. Hence, a reduction in $V_{\text{sub.OH}}$ and supply of an excess amount of oxygen do not occur in the region **230ba** and the region **230bb** in the microwave treatment, preventing a decrease in carrier concentration.

(99) In particular, the above effect is large when the microwave treatment is performed in an oxygen-containing atmosphere after deposition of an insulating film to be the insulator **250b**. It is also preferable that microwave treatment be performed in an oxygen-containing atmosphere after deposition of an insulating film to be the insulator **250a** and another microwave treatment be further performed in an oxygen-containing atmosphere after the deposition of the insulating film to be the insulator **250b**. By performing the microwave treatment in an oxygen-containing atmosphere through the insulator **250a** or the insulator **250b** in such a manner, oxygen can be efficiently implanted into the region **230bc**. The oxygen implanted into the region **230bc** has any of a variety of forms such as an oxygen atom, an oxygen molecule, an oxygen radical (an atom, a molecule, or an ion having an unpaired electron). Note that the oxygen implanted into the region **230bc** has any one or more of the above forms, particularly preferably an oxygen radical. Furthermore, when the microwave treatment is performed in an oxygen-containing atmosphere after the deposition of the insulating film to be the insulator **250b**, the film quality of the insulator **250a** and the insulator **250b** can be improved, leading to higher reliability of the transistor **200**.

(100) In the above manner, oxygen vacancies and $V_{\text{sub.OH}}$ can be selectively removed from the

region **230bc** of the oxide semiconductor, whereby the region **230bc** can be an i-type or substantially i-type region. Furthermore, supply of an excess amount of oxygen to the region **230ba** and the region **230bb** functioning as the source region and the drain region can be inhibited and the n-type regions can be maintained. As a result, a change in the electrical characteristics of the transistor **200** can be inhibited, and thus a variation in the electrical characteristics of the transistors **200** in the substrate plane can be inhibited.

(101) With the above structure, a semiconductor device with a small variation in transistor characteristics can be provided. A semiconductor device with favorable reliability can also be provided. A semiconductor device having favorable electrical characteristics can be provided.

(102) FIG. **1** and the like illustrate the structure in which a side surface of the opening in which the conductor **260** and the like are embedded is substantially perpendicular to the formation surface of the oxide **230b** including a groove portion of the oxide **230b**; however, this embodiment is not limited thereto. For example, a bottom portion of the opening may have a U-shape with a moderate curve. For example, the side surface of the opening may be tilted with respect to the formation surface of the oxide **230b**.

(103) As illustrated in FIG. **1C**, a curved surface may be provided between a side surface of the oxide **230b** and a top surface of the oxide **230b** in a cross-sectional view of the transistor **200** in the channel width direction. In other words, an end portion of the side surface and an end portion of the top surface may be curved (hereinafter referred to as rounded).

(104) The radius of curvature of the curved surface is preferably greater than 0 nm and less than the thickness of the oxide **230b** in a region overlapped by the conductor **242**, or less than half of the length of a region that does not have the curved surface. Specifically, the radius of curvature of the curved surface is greater than 0 nm and less than or equal to 20 nm, preferably greater than or equal to 1 nm and less than or equal to 15 nm, and further preferably greater than or equal to 2 nm and less than or equal to 10 nm. Such a shape can improve the coverage of the oxide **230b** with the insulator **250** and the conductor **260**.

(105) The oxide **230** preferably has a stacked-layer structure of a plurality of oxide layers with different chemical compositions. Specifically, the atomic ratio of the element M to a metal element that is a main component in the metal oxide used as the oxide **230a** is preferably greater than the atomic ratio of the element M to a metal element that is a main component in the metal oxide used as the oxide **230b**. Moreover, the atomic ratio of the element M to In in the metal oxide used as the oxide **230a** is preferably greater than the atomic ratio of the element M to In in the metal oxide used as the oxide **230b**. Furthermore, the atomic ratio of In to the element M in the metal oxide used as the oxide **230b** is preferably greater than the atomic ratio of In to the element M in the metal oxide used as the oxide **230a**.

(106) The oxide **230b** is preferably an oxide having crystallinity, such as a CAAC-OS. An oxide having crystallinity, such as a CAAC-OS, has a dense structure with small amounts of impurities and defects (e.g., oxygen vacancies) and high crystallinity. This can inhibit oxygen extraction from the oxide **230b** by the source electrode or the drain electrode. This can reduce oxygen extraction from the oxide **230b** even when heat treatment is performed; thus, the transistor **200** is stable with respect to high temperatures in a manufacturing process (what is called thermal budget).

(107) Here, the conduction band minimum gradually changes at a junction portion of the oxide **230a** and the oxide **230b**. In other words, the conduction band minimum at the junction portion of the oxide **230a** and the oxide **230b** continuously changes or is continuously connected. To achieve this, the density of defect states in a mixed layer formed at the interface between the oxide **230a** and the oxide **230b** is preferably made low.

(108) Specifically, when the oxide **230a** and the oxide **230b** contain a common element as a main component besides oxygen, a mixed layer with a low density of defect states can be formed. For example, in the case where the oxide **230b** is an In-M-Zn oxide, an In-M-Zn oxide, an M-Zn oxide, an oxide of the element M, an In—Zn oxide, indium oxide, or the like may be used as the oxide

230a.

(109) Specifically, as the oxide **230a**, a metal oxide with a composition of In:M:Zn=1:3:4 [atomic ratio] or in the neighborhood thereof, or a composition of In:M:Zn=1:1:0.5 [atomic ratio] or in the neighborhood thereof is used. As the oxide **230b**, a metal oxide with a composition of In:M:Zn=1:1:1 [atomic ratio] or in the neighborhood thereof, or a composition of In:M:Zn=4:2:3 [atomic ratio] or in the neighborhood thereof is used. Note that a composition in the neighborhood includes the range of $\pm 30\%$ of an intended atomic ratio. Gallium is preferably used as the element M.

(110) When the metal oxide is deposited by a sputtering method, the above atomic ratio is not limited to the atomic ratio of the deposited metal oxide and may be the atomic ratio of a sputtering target used for depositing the metal oxide.

(111) When the oxide **230a** and the oxide **230b** have the above structure, the density of defect states at the interface between the oxide **230a** and the oxide **230b** can be made low. Thus, the influence of interface scattering on carrier conduction is small, and the transistor **200** can have a high on-state current and excellent frequency characteristics.

(112) At least one of the insulator **212**, the insulator **214**, the insulator **271**, the insulator **272**, the insulator **282**, the insulator **283**, the insulator **284**, and the insulator **286** preferably functions as a barrier insulating film, which inhibits diffusion of impurities such as water and hydrogen from the substrate side or above the transistor **200** into the transistor **200**. Thus, for at least one of the insulator **212**, the insulator **214**, the insulator **271**, the insulator **272**, the insulator **282**, the insulator **283**, the insulator **284**, and the insulator **286**, it is preferable to use an insulating material having a function of inhibiting diffusion of impurities such as hydrogen atoms, hydrogen molecules, water molecules, nitrogen atoms, nitrogen molecules, nitrogen oxide molecules (e.g., N.sub.2O, NO, or NO.sub.2), or copper atoms (through which the impurities are less likely to pass). Alternatively, it is preferable to use an insulating material having a function of inhibiting diffusion of oxygen (e.g., at least one of oxygen atoms, oxygen molecules, and the like) (through which the oxygen is less likely to pass).

(113) Note that in this specification, a barrier insulating film refers to an insulating film having a barrier property. A barrier property in this specification means a function of inhibiting diffusion of a targeted substance (also referred to as having low permeability). Alternatively, a barrier property in this specification means a function of capturing and fixing (also referred to as gettering) a targeted substance.

(114) An insulator having a function of inhibiting diffusion of oxygen and impurities such as water and hydrogen is preferably used for the insulator **212**, the insulator **214**, the insulator **271**, the insulator **272**, the insulator **282**, the insulator **283**, the insulator **284**, and the insulator **286**; for example, aluminum oxide, magnesium oxide, hafnium oxide, gallium oxide, indium gallium zinc oxide, silicon nitride, or silicon nitride oxide can be used. For example, silicon nitride, which has a higher hydrogen barrier property, is preferably used for the insulator **212**, the insulator **272**, the insulator **283**, and the insulator **286**. For example, aluminum oxide or magnesium oxide, which has a function of capturing or fixing hydrogen, is preferably used for the insulator **214**, the insulator **271**, the insulator **282**, and the insulator **284**. In this case, impurities such as water and hydrogen can be inhibited from diffusing to the transistor **200** side from the substrate side through the insulator **212** and the insulator **214**. Impurities such as water and hydrogen can be inhibited from diffusing to the transistor **200** side from an interlayer insulating film and the like which are provided outside the insulator **286**. Alternatively, oxygen contained in the insulator **224** and the like can be inhibited from diffusing to the substrate side through the insulator **212** and the insulator **214**. Alternatively, oxygen contained in the insulator **280** and the like can be inhibited from diffusing to above the transistor **200** through the insulator **282** and the like. In this manner, it is preferable that the transistor **200** be surrounded by the insulator **212**, the insulator **214**, the insulator **271**, the insulator **272**, the insulator **282**, the insulator **283**, the insulator **284**, and the insulator **286**, which

have a function of inhibiting diffusion of oxygen and impurities such as water and hydrogen.

(115) Here, an oxide having an amorphous structure is preferably used for the insulator **212**, the insulator **214**, the insulator **271**, the insulator **272**, the insulator **282**, the insulator **283**, the insulator **284**, and the insulator **286**. For example, a metal oxide such as AlO.sub.x (x is a given number greater than 0) or MgO.sub.y (y is a given number greater than 0) is preferably used. In such a metal oxide having an amorphous structure, an oxygen atom has a dangling bond and sometimes has a property of capturing or fixing hydrogen with the dangling bond. When such a metal oxide having an amorphous structure is used as the component of the transistor **200** or provided around the transistor **200**, hydrogen contained in the transistor **200** or hydrogen present around the transistor **200** can be captured or fixed. In particular, hydrogen contained in the channel formation region of the transistor **200** is preferably captured or fixed. The metal oxide having an amorphous structure is used as the component of the transistor **200** or provided around the transistor **200**, whereby the transistor **200** and a semiconductor device which have favorable characteristics and high reliability can be manufactured.

(116) Although each of the insulator **212**, the insulator **214**, the insulator **271**, the insulator **272**, the insulator **282**, the insulator **283**, the insulator **284**, and the insulator **286** preferably has an amorphous structure, a region having a polycrystalline structure may be partly formed.

Alternatively, each of the insulator **212**, the insulator **214**, the insulator **271**, the insulator **272**, the insulator **282**, the insulator **283**, the insulator **284**, and the insulator **286** may have a multilayer structure in which a layer having an amorphous structure and a layer having a polycrystalline structure are stacked. For example, a stacked-layer structure in which a layer having a polycrystalline structure is formed over a layer having an amorphous structure may be employed.

(117) The insulator **212**, the insulator **214**, the insulator **271**, the insulator **272**, the insulator **282**, the insulator **283**, the insulator **284**, and the insulator **286** can be deposited by a sputtering method, for example. Since a sputtering method does not need to use hydrogen as a deposition gas, the hydrogen concentrations in the insulator **212**, the insulator **214**, the insulator **271**, the insulator **272**, the insulator **282**, the insulator **283**, the insulator **284**, and the insulator **286** can be reduced. Note that the deposition method is not limited to a sputtering method, and a chemical vapor deposition (CVD) method, a molecular beam epitaxy (MBE) method, a pulsed laser deposition (PLD) method, an atomic layer deposition (ALD) method, or the like can be used as appropriate.

(118) The resistivities of the insulator **212**, the insulator **272**, the insulator **283**, and the insulator **286** are preferably low in some cases. For example, by setting the resistivities of the insulator **212**, the insulator **272**, the insulator **283**, and the insulator **286** to approximately $1 \times 10^{13} \Omega\text{cm}$, the insulator **212**, the insulator **272**, the insulator **283**, and the insulator **286** can sometimes reduce charge up of the conductor **205**, the conductor **242**, the conductor **260**, or the conductor **246** in treatment using plasma or the like in the manufacturing process of a semiconductor device. The resistivities of the insulator **212**, the insulator **272**, the insulator **283**, and the insulator **286** are preferably higher than or equal to $1 \times 10^{10} \Omega\text{cm}$ and lower than or equal to $1 \times 10^{15} \Omega\text{cm}$.

(119) The insulator **216**, the insulator **274**, and the insulator **280** each preferably have a lower permittivity than the insulator **214**. When a material with a low permittivity is used for an interlayer film, parasitic capacitance generated between wirings can be reduced. For the insulator **216**, the insulator **274**, and the insulator **280**, silicon oxide, silicon oxynitride, silicon oxide to which fluorine is added, silicon oxide to which carbon is added, silicon oxide to which carbon and nitrogen are added, porous silicon oxide, or the like is used as appropriate, for example.

(120) The conductor **205** is placed to be overlapped by the oxide **230** and the conductor **260**. Here, the conductor **205** is preferably provided to be embedded in an opening formed in the insulator **216**.

(121) The conductor **205** includes the conductor **205a**, the conductor **205b**, and the conductor **205c**. The conductor **205a** is provided in contact with a bottom surface and a sidewall of the opening. The conductor **205b** is provided to be embedded in a recessed portion formed in the conductor **205a**.

Here, a top surface of the conductor **205b** is lower in level than a top surface of the conductor **205a** and a top surface of the insulator **216**. The conductor **205c** is provided in contact with the top surface of the conductor **205b** and a side surface of the conductor **205a**. Here, the level of a top surface of the conductor **205c** is substantially the same as the level of the top surface of the conductor **205a** and the level of the top surface of the insulator **216**. That is, the conductor **205b** is surrounded by the conductor **205a** and the conductor **205c**.

(122) Here, for the conductor **205a** and the conductor **205c**, it is preferable to use a conductive material having a function of inhibiting diffusion of impurities such as a hydrogen atom, a hydrogen molecule, a water molecule, a nitrogen atom, a nitrogen molecule, a nitrogen oxide molecule (N.sub.2O, NO, NO.sub.2, or the like), and a copper atom. Alternatively, it is preferable to use a conductive material having a function of inhibiting diffusion of oxygen (e.g., at least one of an oxygen atom, an oxygen molecule, and the like).

(123) When the conductor **205a** and the conductor **205c** are formed using a conductive material having a function of inhibiting diffusion of hydrogen, impurities such as hydrogen contained in the conductor **205b** can be prevented from diffusing into the oxide **230** through the insulator **224** and the like. When the conductor **205a** and the conductor **205c** are formed using a conductive material having a function of inhibiting diffusion of oxygen, the conductivity of the conductor **205b** can be inhibited from being lowered because of oxidation. As the conductive material having a function of inhibiting diffusion of oxygen, for example, titanium, titanium nitride, tantalum, tantalum nitride, ruthenium, or ruthenium oxide is preferably used. Thus, a single layer or a stacked layer of the above conductive material is used as the conductor **205a**. For example, titanium nitride is used for the conductor **205a**.

(124) Moreover, the conductor **205b** is preferably formed using a conductive material containing tungsten, copper, or aluminum as its main component. For example, tungsten is used for the conductor **205b**.

(125) The conductor **205** sometimes functions as a second gate electrode. In that case, by changing a potential applied to the conductor **205** not in conjunction with but independently of a potential applied to the conductor **260**, the threshold voltage (V_{th}) of the transistor **200** can be controlled. In particular, V_{th} of the transistor **200** can be higher in the case where a negative potential is applied to the conductor **205**, and the off-state current can be reduced. Thus, a drain current at the time when a potential applied to the conductor **260** is 0 V can be lower in the case where a negative potential is applied to the conductor **205** than in the case where the negative potential is not applied to the conductor **205**.

(126) The electric resistivity of the conductor **205** is designed in consideration of the potential applied to the conductor **205**, and the thickness of the conductor **205** is determined in accordance with the electric resistivity. The thickness of the insulator **216** is substantially equal to that of the conductor **205**. The conductor **205** and the insulator **216** are preferably as thin as possible in the allowable range of the design of the conductor **205**. When the thickness of the insulator **216** is reduced, the absolute amount of impurities such as hydrogen contained in the insulator **216** can be reduced, inhibiting the diffusion of the impurities into the oxide **230**.

(127) As illustrated in FIG. 1A, the conductor **205** is preferably provided to be larger than a region of the oxide **230** that is not overlapped by the conductor **242a** or the conductor **242b**. As illustrated in FIG. 1C, it is particularly preferable that the conductor **205** extend to a region outside end portions of the oxide **230a** and the oxide **230b** in the channel width direction. That is, the conductor **205** and the conductor **260** preferably overlap each other with the insulators therebetween on the outer side of a side surface of the oxide **230** in the channel width direction. With this structure, the channel formation region of the oxide **230** can be electrically surrounded by the electric field of the conductor **260** functioning as a first gate electrode and the electric field of the conductor **205** functioning as the second gate electrode. In this specification, a transistor structure in which a channel formation region is electrically surrounded by electric fields of a first gate and a second

gate is referred to as a surrounded channel (S-channel) structure.

(128) In this specification and the like, a transistor having the S-channel structure refers to a transistor having a structure in which a channel formation region is electrically surrounded by the electric fields of a pair of gate electrodes. The S-channel structure disclosed in this specification and the like is different from a Fin-type structure and a planar structure. With the S-channel structure, resistance to a short-channel effect can be enhanced, that is, a transistor in which a short-channel effect is less likely to occur can be provided.

(129) Furthermore, as illustrated in FIG. 1C, the conductor **205** is extended to function as a wiring as well. However, without limitation to this structure, a structure in which a conductor functioning as a wiring is provided below the conductor **205** may be employed. In addition, the conductor **205** is not necessarily provided in each transistor. For example, the conductor **205** may be shared by a plurality of transistors.

(130) Although the transistor **200** having a structure in which the conductor **205** is a stack of the conductor **205a**, the conductor **205b**, and the conductor **205c** is illustrated, the present invention is not limited thereto. For example, the conductor **205** may be provided to have a single-layer structure or a stacked-layer structure of two layers or four or more layers.

(131) The insulator **222** and the insulator **224** function as a gate insulator.

(132) It is preferable that the insulator **222** have a function of inhibiting diffusion of hydrogen (e.g., at least one of a hydrogen atom, a hydrogen molecule, and the like). In addition, it is preferable that the insulator **222** have a function of inhibiting diffusion of oxygen (e.g., at least one of an oxygen atom, an oxygen molecule, and the like). For example, the insulator **222** preferably has a function of inhibiting diffusion of one or both of hydrogen and oxygen more than the insulator **224**.

(133) As the insulator **222**, an insulator containing an oxide of one or both of aluminum and hafnium, which is an insulating material, is preferably used. For the insulator, aluminum oxide, hafnium oxide, an oxide containing aluminum and hafnium (hafnium aluminate), or the like is preferably used. In the case where the insulator **222** is formed using such a material, the insulator **222** functions as a layer that inhibits release of oxygen from the oxide **230** to the substrate side and diffusion of impurities such as hydrogen from the periphery of the transistor **200** into the oxide **230**. Thus, providing the insulator **222** can inhibit diffusion of impurities such as hydrogen inside the transistor **200** and inhibit generation of oxygen vacancies in the oxide **230**. Moreover, the conductor **205** can be inhibited from reacting with oxygen contained in the insulator **224** and the oxide **230**.

(134) Alternatively, aluminum oxide, bismuth oxide, germanium oxide, niobium oxide, silicon oxide, titanium oxide, tungsten oxide, yttrium oxide, or zirconium oxide may be added to the above insulator, for example. Alternatively, the insulator may be subjected to nitriding treatment. A stack of silicon oxide, silicon oxynitride, or silicon nitride over these insulators may be used for the insulator **222**.

(135) For example, a single layer or stacked layers of an insulator containing what is called a high-k material such as aluminum oxide, hafnium oxide, tantalum oxide, zirconium oxide, lead zirconate titanate (PZT), strontium titanate (SrTiO₃), or (Ba,Sr)TiO₃ (BST) may be used for the insulator **222**. As miniaturization and high integration of transistors progress, a problem such as a leakage current may arise because of a thinner gate insulator. When a high-k material is used for an insulator functioning as the gate insulator, a gate potential at the time when the transistor operates can be reduced while the physical thickness is maintained.

(136) Silicon oxide or silicon oxynitride, for example, can be used as appropriate for the insulator **224** that is in contact with the oxide **230**.

(137) In a manufacturing process of the transistor **200**, heat treatment is preferably performed with a surface of the oxide **230** exposed. For example, the heat treatment is performed at a temperature higher than or equal to 100° C. and lower than or equal to 600° C., preferably higher than or equal to 350° C. and lower than or equal to 550° C. Note that the heat treatment is performed in a

nitrogen gas or inert gas atmosphere, or an atmosphere containing an oxidizing gas at 10 ppm or more, 1% or more, or 10% or more. For example, the heat treatment is preferably performed in an oxygen atmosphere. This can supply oxygen to the oxide **230** to reduce oxygen vacancies (V.sub.O). The heat treatment may be performed under reduced pressure. Alternatively, the heat treatment may be performed in such a manner that heat treatment is performed in a nitrogen gas or inert gas atmosphere, and then another heat treatment is performed in an atmosphere containing an oxidizing gas at 10 ppm or more, 1% or more, or 10% or more in order to compensate for released oxygen. Alternatively, the heat treatment may be performed in such a manner that heat treatment is performed in an atmosphere containing an oxidizing gas at 10 ppm or more, 1% or more, or 10% or more, and then another heat treatment is successively performed in a nitrogen gas or inert gas atmosphere.

(138) Note that oxygen adding treatment performed on the oxide **230** can promote a reaction in which oxygen vacancies in the oxide **230** are repaired with supplied oxygen, i.e., a reaction of "V.sub.O+O.fwdarw.null". Furthermore, hydrogen remaining in the oxide **230** reacts with supplied oxygen, so that the hydrogen can be removed as H.sub.2O (dehydration). This can inhibit recombination of hydrogen remaining in the oxide **230** with oxygen vacancies and formation of V.sub.OH.

(139) Note that the insulator **222** and the insulator **224** may each have a stacked-layer structure of two or more layers. In that case, without limitation to a stacked-layer structure formed of the same material, a stacked-layer structure formed of different materials may be employed. The insulator **224** may be formed into an island shape so as to be overlapped by the oxide **230a**. In this case, the insulator **272** is in contact with a side surface of the insulator **224** and a top surface of the insulator **222**.

(140) The oxide **243a** and the oxide **243b** are provided over the oxide **230b**. The oxide **243a** and the oxide **243b** are provided to be apart from each other with the conductor **260** therebetween.

(141) The oxide **243** (the oxide **243a** and the oxide **243b**) preferably has a function of inhibiting passage of oxygen. The oxide **243** having a function of inhibiting passage of oxygen is preferably placed between the oxide **230b** and the conductor **242** functioning as the source electrode and the drain electrode, in which case the electric resistance between the oxide **230b** and the conductor **242** can be reduced. Such a structure improves the electrical characteristics of the transistor **200** and the reliability of the transistor **200**. In the case where the electric resistance between the oxide **230b** and the conductor **242** can be sufficiently reduced, the oxide **243** is not necessarily provided.

(142) A metal oxide containing the element M may be used as the oxide **243**. In particular, aluminum, gallium, yttrium, or tin is preferably used as the element M. The concentration of the element M in the oxide **243** is preferably higher than that in the oxide **230b**. Furthermore, gallium oxide may be used for the oxide **243**. A metal oxide such as an In-M-Zn oxide may be used as the oxide **243**. Specifically, the atomic ratio of the element M to In in the metal oxide used as the oxide **243** is preferably greater than the atomic ratio of the element M to In in the metal oxide used as the oxide **230b**. The thickness of the oxide **243** is preferably greater than or equal to 0.5 nm and less than or equal to 5 nm, further preferably greater than or equal to 1 nm and less than or equal to 3 nm, still further preferably greater than or equal to 1 nm and less than or equal to 2 nm. The oxide **243** preferably has crystallinity. In the case where the oxide **243** has crystallinity, release of oxygen from the oxide **230** can be favorably inhibited. When the oxide **243** has a hexagonal crystal structure, for example, release of oxygen from the oxide **230** can sometimes be inhibited.

(143) It is preferable that the conductor **242a** be provided in contact with a top surface of the oxide **243a** and the conductor **242b** be provided in contact with a top surface of the oxide **243b**. Each of the conductor **242a** and the conductor **242b** functions as a source electrode or a drain electrode of the transistor **200**.

(144) For the conductor **242** (the conductor **242a** and the conductor **242b**), for example, a nitride containing tantalum, a nitride containing titanium, a nitride containing molybdenum, a nitride

containing tungsten, a nitride containing tantalum and aluminum, a nitride containing titanium and aluminum, or the like is preferably used. In one embodiment of the present invention, a nitride containing tantalum is particularly preferable. As another example, ruthenium oxide, ruthenium nitride, an oxide containing strontium and ruthenium, or an oxide containing lanthanum and nickel may be used. These materials are preferable because they are each a conductive material that is not easily oxidized or a material that maintains the conductivity even after absorbing oxygen.

(145) Note that hydrogen contained in the oxide **230b** or the like diffuses into the conductor **242a** or the conductor **242b** in some cases. In particular, when a nitride containing tantalum is used for the conductor **242a** and the conductor **242b**, hydrogen contained in the oxide **230b** or the like is likely to diffuse into the conductor **242a** or the conductor **242b**, and the diffused hydrogen is bonded to nitrogen contained in the conductor **242a** or the conductor **242b** in some cases. That is, hydrogen contained in the oxide **230b** or the like is absorbed by the conductor **242a** or the conductor **242b** in some cases.

(146) No curved surface is preferably formed between a side surface of the conductor **242** and a top surface of the conductor **242**. When no curved surface is formed in the conductor **242**, the conductor **242** can have a large cross-sectional area in the channel width direction as illustrated in FIG. **1D**. Accordingly, the conductivity of the conductor **242** is increased, so that the on-state current of the transistor **200** can be increased.

(147) The insulator **271a** is provided in contact with the top surface of the conductor **242a**, and the insulator **271b** is provided in contact with the top surface of the conductor **242b**. The insulator **271** preferably functions as at least a barrier insulating film against oxygen. Thus, the insulator **271** preferably has a function of inhibiting oxygen diffusion. For example, the insulator **271** preferably has a function of inhibiting diffusion of oxygen more than the insulator **280**. For example, a nitride containing silicon such as silicon nitride may be used for the insulator **271**. The insulator **271** preferably has a function of capturing impurities such as hydrogen. In that case, for the insulator **271**, a metal oxide having an amorphous structure, for example, an insulator such as aluminum oxide or magnesium oxide, may be used. It is particularly preferable to use aluminum oxide having an amorphous structure or amorphous aluminum oxide for the insulator **271** because hydrogen can be captured or fixed more effectively in some cases. Accordingly, the transistor **200** and a semiconductor device which have favorable characteristics and high reliability can be manufactured.

(148) The insulator **272** is provided to cover the insulator **224**, the oxide **230a**, the oxide **230b**, the oxide **243**, the conductor **242**, and the insulator **271**. The insulator **272** preferably has a function of capturing and fixing hydrogen. In that case, the insulator **272** preferably includes silicon nitride, or a metal oxide having an amorphous structure, for example, an insulator such as aluminum oxide or magnesium oxide.

(149) When the above insulator **271** and the insulator **272** are provided, the conductor **242** can be surrounded by the insulators having a barrier property against oxygen. That is, oxygen contained in the insulator **224** and the insulator **280** can be prevented from diffusing into the conductor **242**. As a result, the conductor **242** can be inhibited from being directly oxidized by oxygen contained in the insulator **224** and the insulator **280**, so that an increase in resistivity and a reduction in on-state current can be inhibited.

(150) The insulator **250** functions as a gate insulator. The insulator **250** is preferably placed in contact with the top surface of the oxide **230b**. For the insulator **250**, silicon oxide, silicon oxynitride, silicon nitride oxide, silicon nitride, silicon oxide to which fluorine is added, silicon oxide to which carbon is added, silicon oxide to which carbon and nitrogen are added, porous silicon oxide, or the like can be used. In particular, silicon oxide and silicon oxynitride are preferable because they are thermally stable.

(151) As in the insulator **224**, the concentration of impurities such as water and hydrogen in the insulator **250** (the insulator **250a** and the insulator **250b**) is preferably reduced. The thickness of the

insulator **250** is preferably greater than or equal to 1 nm and less than or equal to 20 nm. In particular, the thickness of the insulator **250a** is preferably greater than or equal to 0.5 nm and less than or equal to 15.0 nm.

(152) In the case where the insulator **250** has a stacked-layer structure of two layers as illustrated in FIG. 1B and FIG. 1C, it is preferable that the insulator **250a** that is a lower layer be formed using an insulator that is likely to transmit oxygen and the insulator **250b** that is an upper layer be formed using an insulator having a function of inhibiting oxygen diffusion. With such a structure, oxygen contained in the insulator **250a** can be inhibited from diffusing into the conductor **260**. That is, a reduction in the amount of oxygen supplied to the oxide **230** can be inhibited. In addition, oxidation of the conductor **260** due to oxygen contained in the insulator **250a** can be inhibited. For example, it is preferable that the insulator **250a** be provided using any of the above-described materials that can be used for the insulator **250** and the insulator **250b** be provided using an insulator containing an oxide of one or both of aluminum and hafnium. As the insulator, aluminum oxide, hafnium oxide, an oxide containing aluminum and hafnium (hafnium aluminate), an oxide containing aluminum and silicon (hafnium silicate), or the like can be used. In this embodiment, hafnium oxide is used as the insulator **250b**. The thickness of the insulator **250b** is greater than or equal to 0.5 nm and less than or equal to 5.0 nm, preferably greater than or equal to 1.0 nm and less than or equal to 5.0 nm, further preferably greater than or equal to 1.0 nm and less than or equal to 3.0 nm.

(153) The insulator **250a** is preferably formed by a PEALD method using a gas **401** (precursor) containing silicon but not containing hydrocarbon and an oxidizing gas **402** (reactant). A rare gas such as helium, neon, argon, krypton, or xenon may be added to the reactant.

(154) ALD methods include a thermal ALD method, in which a precursor and a reactant react with each other only by a thermal energy, a PEALD (Plasma Enhanced ALD) method, in which a plasma-excited reactant is used, and the like.

(155) An ALD method, which enables one atomic layer to be deposited at a time using self-regulating characteristics of atoms, has advantages such as deposition of an extremely thin film, deposition on a component with a high aspect ratio, deposition of a film with a small number of defects such as pinholes, deposition with excellent coverage, and low-temperature deposition.

(156) The use of plasma in a PEALD method is sometimes preferable because deposition at a lower temperature is possible. Note that a precursor used in an ALD method sometimes contains carbon or the like. Thus, in some cases, a film provided by an ALD method contains impurities such as carbon in a larger amount than a film provided by another deposition method. Note that impurities can be quantified by secondary ion mass spectrometry (SIMS) or X-ray photoelectron spectroscopy (XPS).

(157) In this embodiment, a PEALD method is used. As the gas **401** containing silicon but not containing hydrocarbon, SiH₄, Si₂H₆, SiF₄, SiCl₄, SiBr₄, SiH₂Cl₂, SiH₂I₂, or the like can be used. As the oxidizing gas **402**, O₂, O₃, N₂O, NO₂, H₂O, or the like can be used. In this embodiment, SiH₄ and N₂O are used as the gas **401** containing silicon but not containing hydrocarbon and the oxidizing gas **402**, respectively.

(158) FIG. 5 is a flow chart showing a process in which silicon oxide to be the insulator **250a** is formed by a PEALD method using SiH₄ as the gas **401** containing silicon but not containing hydrocarbon and N₂O as the oxidizing gas **402**, and FIG. 6A and FIG. 6B show deposition sequences.

(159) First, SiH₄ and N₂O are introduced into a reaction chamber, and the pressure in the reaction chamber is kept constant (Step S01). Here, helium may be introduced. In the flow rate ratio of SiH₄ and N₂O, when the flow rate of SiH₄ is 1, the flow rate of N₂O is higher than or equal to 10 and lower than or equal to 3000, preferably higher than or equal to 10 and lower than or equal to 800, further preferably higher than or equal to 50 and lower than or

equal to 400. When the flow rate of N.sub.2O is higher than or equal to 50, generation of NOx can be inhibited in the insulator **250a**. The pressure in the reaction chamber is higher than or equal to 200 Pa and lower than or equal to 1200 Pa, preferably higher than or equal to 400 Pa and lower than or equal to 1000 Pa, further preferably higher than or equal to 600 Pa and lower than or equal to 800 Pa. The substrate temperature is higher than or equal to 100° C. and lower than or equal to 500° C., preferably higher than or equal to 200° C. and lower than or equal to 400° C. The substrate is not necessarily heated, and deposition may be performed at room temperature.

(160) Next, the introduction of SiH.sub.4 is stopped, and SiH.sub.4 remaining in the reaction chamber is purged (Step **S02**).

(161) Next, high-frequency power **403** is applied to the reaction chamber, and plasma due to N.sub.2O is generated. The high frequency is higher than or equal to 13.56 MHz and lower than or equal to 60 MHz. When SiH.sub.X adsorbed onto the substrate in Step **S01** is oxidized by N.sub.2O plasma, silicon oxide of approximately one molecule layer can be formed (Step **S03**). Note that nitrogen implanted by N.sub.2O plasma is contained in the silicon oxide in some cases. Silicon oxide containing nitrogen is referred to as silicon oxynitride in some cases.

(162) Next, application of the high-frequency power **403** is stopped (Step **S04**).

(163) When Step **S01** to Step **S04** described above are regarded as one cycle and repeated until a desired thickness is obtained, silicon oxide to be the insulator **250a** can be formed. The number of cycles is more than or equal to 1 and less than or equal to 500. Note that the number of cycles may be determined as appropriate depending on the desired thickness of the insulator **250a**. As shown in FIG. **6B**, in Step **S02**, a step of evacuation to a vacuum may be added in which the introduction of SiH.sub.4 and N.sub.2O is stopped and SiH.sub.4 and N.sub.2O remaining in the reaction chamber are evacuated. At this time, the introduction of SiH.sub.4 and the introduction of N.sub.2O may be concurrently stopped, or the introduction of N.sub.2O may be stopped after stopping the introduction of SiH.sub.4. The introduction of N.sub.2O is preferably restarted before the start of Step **S03**.

(164) The silicon oxide to be the insulator **250a** that is formed in the above manner enables formation of a favorable insulator with reduced concentrations of hydrogen and carbon as compared with silicon oxide that is formed by a PECVD method using SiH.sub.4 and N.sub.2O.

(165) In the PECVD method using SiH.sub.4 and N.sub.2O, high-frequency power is applied in the state where SiH.sub.4 and N.sub.2O are introduced to generate plasma, so that SiH.sub.4 is decomposed in the plasma and a large number of hydrogen radicals are generated, and thus hydrogen enters the silicon oxide to be the insulator **250a**. In addition, the insulator **250a** is in contact with the region **230bc** functioning as the channel formation region as illustrated in FIG. **3**; therefore, when oxygen in the region **230bc** is extracted by reduction reaction of hydrogen radicals to form V.sub.OH, the hydrogen concentration in the region **230bc** is increased.

(166) In contrast, in the PEALD method using SiH.sub.4 and N.sub.2O that is one embodiment of the present invention, high-frequency power is not applied while SiH.sub.4 and N.sub.2O are introduced in Step **01** above, remaining SiH.sub.4 is purged in Step **02**, and then high-frequency power is applied in the state where only N.sub.2O is introduced to generate plasma in Step **03**; thus, generation of hydrogen radicals can be inhibited. Accordingly, entry of hydrogen into the silicon oxide to be the insulator **250a** and the region **230bc** in contact with the silicon oxide to be the insulator **250a** can be inhibited. In the PEALD method using SiH.sub.4 and N.sub.2O, SiH.sub.4 is used as a precursor, and a precursor containing an impurity such as carbon, e.g., an organic precursor having a CH group, is not used; thus, entry of hydrocarbon, an impurity such as carbon, or the like into the silicon oxide to be the insulator **250a** can be inhibited. The silicon oxide formed in such a manner is a denser film with a reduced impurity concentration, and thus diffusion of In from the region **230bc** in the oxide **230b** into the silicon oxide to be the insulator **250a** can be prevented.

(167) The carbon concentration in the silicon oxide to be the insulator **250a** is preferably higher

than or equal to 1×10^{18} atoms/cm³ and lower than or equal to 5×10^{20} atoms/cm³, further preferably higher than or equal to 5×10^{18} atoms/cm³ and lower than or equal to 1×10^{20} atoms/cm³ in the analysis by SIMS. The silicon oxide to be the insulator **250a** contains nitrogen, and the nitrogen concentration is preferably higher than or equal to 1×10^{19} atoms/cm³ and lower than or equal to 1×10^{21} atoms/cm³, further preferably higher than or equal to 3×10^{19} atoms/cm³ and lower than or equal to 2×10^{20} atoms/cm³ in SIMS analysis. Furthermore, the concentration of In contained in the silicon oxide to be the insulator **250a** is preferably lower than or equal to 1.0×10^{19} atoms/cm³, further preferably lower than or equal to 1.0×10^{18} atoms/cm³, still further preferably lower than or equal to 1.0×10^{17} atoms/cm³ in SIMS analysis.

(168) Note that in the case where silicon oxide to be the insulator **250a** is in contact with the oxide **230b**, the above carbon concentration, nitrogen concentration, and In concentration in the insulator are concentrations in a region at a distance of greater than or equal to 1 nm from an interface between the silicon oxide and the oxide **230b** in some cases.

(169) As described above, when the silicon oxide to be the insulator **250a** is formed by the PEALD method, which is one embodiment of the present invention, using a gas (precursor) containing silicon but not containing hydrocarbon and an oxidizing gas (reactant), a transistor can have excellent electric characteristics and high reliability.

(170) In the case where silicon oxide, silicon oxynitride, or the like is used for the insulator **250a**, the insulator **250b** may be formed using an insulating material that is a high-k material having a high relative dielectric constant. The gate insulator having a stacked-layer structure of the insulator **250a** and the insulator **250b** can be thermally stable and can have a high dielectric constant. Thus, a gate potential that is applied during operation of the transistor can be reduced while the physical thickness of the gate insulator is maintained. In addition, the equivalent oxide thickness (EOT) of the insulator functioning as the gate insulator can be reduced.

(171) A metal oxide may be provided between the insulator **250** and the conductor **260**. The metal oxide preferably inhibits diffusion of oxygen from the insulator **250** into the conductor **260**. Providing the metal oxide that inhibits diffusion of oxygen inhibits diffusion of oxygen from the insulator **250** into the conductor **260**. That is, a reduction in the amount of oxygen supplied to the oxide **230** can be inhibited. Moreover, oxidation of the conductor **260** due to oxygen in the insulator **250** can be inhibited.

(172) Note that the metal oxide may function as part of the first gate electrode. For example, a metal oxide that can be used as the oxide **230** can be used as the metal oxide. In that case, when the conductor **260a** is deposited by a sputtering method, the metal oxide can have a reduced electric resistance value to be a conductor. Such a conductor can be referred to as an OC (Oxide Conductor) electrode.

(173) With the metal oxide, the on-state current of the transistor **200** can be increased without a reduction in the influence of the electric field from the conductor **260**. Since a distance between the conductor **260** and the oxide **230** is kept by the physical thicknesses of the insulator **250** and the metal oxide, a leakage current between the conductor **260** and the oxide **230** can be inhibited. Moreover, when the stacked-layer structure of the insulator **250** and the metal oxide is provided, the physical distance between the conductor **260** and the oxide **230** and the intensity of electric field applied to the oxide **230** from the conductor **260** can be easily adjusted as appropriate.

(174) The conductor **260** functions as the first gate electrode of the transistor **200**. The conductor **260** preferably includes the conductor **260a** and the conductor **260b** placed over the conductor **260a**. For example, the conductor **260a** is preferably placed to cover a bottom surface and a side surface of the conductor **260b**. Moreover, as illustrated in FIG. 1B and FIG. 1C, the top surface of the conductor **260** is substantially level with the top surface of the insulator **250**. Although the conductor **260** has a two-layer structure of the conductor **260a** and the conductor **260b** in FIG. 1B and FIG. 1C, the conductor **260** may have a single-layer structure or a stacked-layer structure of

three or more layers.

(175) For the conductor **260a**, a conductive material having a function of inhibiting diffusion of impurities such as a hydrogen atom, a hydrogen molecule, a water molecule, a nitrogen atom, a nitrogen molecule, a nitrogen oxide molecule, and a copper atom is preferably used. Alternatively, it is preferable to use a conductive material having a function of inhibiting diffusion of oxygen (e.g., at least one of an oxygen atom, an oxygen molecule, and the like).

(176) In addition, when the conductor **260a** has a function of inhibiting diffusion of oxygen, the conductivity of the conductor **260b** can be inhibited from being lowered because of oxidation due to oxygen contained in the insulator **250**. As the conductive material having a function of inhibiting diffusion of oxygen, for example, titanium, titanium nitride, tantalum, tantalum nitride, ruthenium, or ruthenium oxide is preferably used.

(177) The conductor **260** also functions as a wiring and thus is preferably formed using a conductor having high conductivity. For example, a conductive material containing tungsten, copper, or aluminum as its main component can be used for the conductor **260b**. The conductor **260b** may have a stacked-layer structure; for example, a stacked-layer structure of the conductive material and titanium or titanium nitride may be employed.

(178) In the transistor **200**, the conductor **260** is formed in a self-aligned manner to fill the opening formed in the insulator **280** and the like. The formation of the conductor **260** in this manner allows the conductor **260** to be placed certainly in a region between the conductor **242a** and the conductor **242b** without alignment.

(179) As illustrated in FIG. **1C**, in the channel width direction of the transistor **200**, with reference to a bottom surface of the insulator **222**, the level of the bottom surface of the conductor **260** in a region where the conductor **260** and the oxide **230b** do not overlap is preferably lower than the level of a bottom surface of the oxide **230b**. When the conductor **260** functioning as the gate electrode covers the side surface and the top surface of the channel formation region of the oxide **230b** with the insulator **250** and the like therebetween, the electric field of the conductor **260** is likely to act on the entire channel formation region of the oxide **230b**. Thus, the on-state current of the transistor **200** can be increased and the frequency characteristics of the transistor **200** can be improved. When the bottom surface of the insulator **222** is a reference, the difference between the level of the bottom surface of the conductor **260** in a region where the conductor **260** do not overlap the oxide **230a** and the oxide **230b** and the level of the bottom surface of the oxide **230b** is greater than or equal to 0 nm and less than or equal to 100 nm, preferably greater than or equal to 3 nm and less than or equal to 50 nm, further preferably greater than or equal to 5 nm and less than or equal to 20 nm.

(180) The insulator **280** is provided over the insulator **272**, and the opening is formed in a region where the insulator **250** and the conductor **260** are to be provided. In addition, the top surface of the insulator **280** may be planarized.

(181) The insulator **280** functioning as an interlayer film preferably has a low permittivity. When a material with a low permittivity is used for an interlayer film, parasitic capacitance generated between wirings can be reduced. The insulator **280** is preferably provided using a material similar to that for the insulator **216**, for example. In particular, silicon oxide and silicon oxynitride, which have thermal stability, are preferable. Materials such as silicon oxide, silicon oxynitride, and porous silicon oxide are particularly preferable because a region containing oxygen released by heating can be easily formed.

(182) The concentration of impurities such as water and hydrogen in the insulator **280** is preferably reduced. Oxide containing silicon such as silicon oxide, silicon oxynitride, or the like is used as appropriate for the insulator **280**, for example.

(183) The insulator **282** and the insulator **284** preferably function as barrier insulating films that inhibit impurities such as water and hydrogen from diffusing into the insulator **280** from above and preferably have a function of capturing impurities such as hydrogen. The insulator **282** and the

insulator **284** preferably function as barrier insulating films that inhibit passage of oxygen. For each of the insulator **282** and the insulator **284**, a metal oxide having an amorphous structure, for example, an insulator such as aluminum oxide can be used. The insulator **282**, which has a function of capturing impurities such as hydrogen, is provided in contact with the insulator **280** in a region sandwiched between the insulator **212** and the insulator **283**, whereby impurities such as hydrogen contained in the insulator **280** and the like can be captured and the amount of hydrogen in the region can be kept constant. It is particularly preferable to use aluminum oxide having an amorphous structure or amorphous aluminum oxide for the insulator **282** and the insulator **284** because hydrogen can be captured or fixed more effectively in some cases. Accordingly, the transistor **200** and a semiconductor device which have favorable characteristics and high reliability can be manufactured.

(184) The insulator **283** functions as a barrier insulating film that inhibits impurities such as water and hydrogen from diffusing into the insulator **280** from above. The insulator **283** is placed over the insulator **282**. The insulator **283** is preferably formed using a nitride containing silicon such as silicon nitride or silicon nitride oxide. For example, silicon nitride deposited by a sputtering method is used for the insulator **283**. When the insulator **283** is deposited by a sputtering method, high-density silicon nitride where a void or the like is less likely to be formed can be formed. To obtain the insulator **283**, silicon nitride deposited by a PEALD method or a CVD method may be stacked over silicon nitride deposited by a sputtering method.

(185) For the conductor **240a** and the conductor **240b**, a conductive material containing tungsten, copper, or aluminum as its main component is preferably used. The conductor **240a** and the conductor **240b** may each have a stacked-layer structure.

(186) In the case where the conductor **240** has a stacked-layer structure, a conductive material having a function of inhibiting passage of impurities such as water and hydrogen is preferably used for a conductor in contact with the insulator **283**, the insulator **284**, the insulator **282**, the insulator **280**, the insulator **272**, and the insulator **271**. For example, tantalum, tantalum nitride, titanium, titanium nitride, ruthenium, ruthenium oxide, or the like is preferably used. The conductive material having a function of inhibiting passage of impurities such as water and hydrogen may be used as a single layer or stacked layers. Moreover, impurities such as water and hydrogen contained in a layer above the insulator **283** can be inhibited from entering the oxide **230** through the conductor **240a** and the conductor **240b**.

(187) For the insulator **241a** and the insulator **241b**, for example, an insulator such as silicon nitride, aluminum oxide, or silicon nitride oxide may be used. Since the insulator **241a** and the insulator **241b** are provided in contact with the insulator **283**, the insulator **284**, the insulator **282**, the insulator **280**, the insulator **272**, and the insulator **271**, impurities such as water and hydrogen contained in the insulator **280** or the like can be inhibited from entering the oxide **230** through the conductor **240a** and the conductor **240b**. In particular, silicon nitride is suitable because of its high blocking property against hydrogen. Furthermore, oxygen contained in the insulator **280** can be prevented from being absorbed by the conductor **240a** and the conductor **240b**.

(188) The conductor **246** (the conductor **246a** and the conductor **246b**) functioning as a wiring may be placed in contact with a top surface of the conductor **240a** and a top surface of the conductor **240b**. The conductor **246** is preferably formed using a conductive material containing tungsten, copper, or aluminum as its main component. Furthermore, the conductor may have a stacked-layer structure and may be a stack of titanium or titanium nitride and the conductive material, for example. Note that the conductor may be formed to be embedded in an opening provided in an insulator.

(189) The insulator **286** is provided over the conductor **246** and the insulator **284**. Accordingly, a top surface of the conductor **246** and a side surface of the conductor **246** are in contact with the insulator **286** and a bottom surface of the conductor **246** is in contact with the insulator **283**. In other words, a structure can be obtained in which the conductor **246** is surrounded by the insulator

283 and the insulator **286**. With such a structure, the passage of oxygen from the outside can be inhibited and the oxidation of the conductor **246** can be prevented. Furthermore, impurities such as water and hydrogen can be prevented from diffusing from the conductor **246** to the outside, which is preferable.

(190) <Constituent Materials of Semiconductor Device>

(191) Constituent materials that can be used for the semiconductor device are described below.

(192) <<Substrate>>

(193) As a substrate where the transistor **200** is formed, an insulator substrate, a semiconductor substrate, or a conductor substrate is used, for example. Examples of the insulator substrate include a glass substrate, a quartz substrate, a sapphire substrate, a stabilized zirconia substrate (e.g., an yttria-stabilized zirconia substrate), and a resin substrate. Examples of the semiconductor substrate include a semiconductor substrate using silicon, germanium, or the like as a material and a compound semiconductor substrate including silicon carbide, silicon germanium, gallium arsenide, indium phosphide, zinc oxide, or gallium oxide. Another example is a semiconductor substrate in which an insulator region is included in the semiconductor substrate, e.g., an SOI (Silicon On Insulator) substrate. Examples of the conductor substrate include a graphite substrate, a metal substrate, an alloy substrate, and a conductive resin substrate. Other examples include a substrate including a metal nitride and a substrate including a metal oxide. Other examples include an insulator substrate provided with a conductor or a semiconductor, a semiconductor substrate provided with a conductor or an insulator, and a conductor substrate provided with a semiconductor or an insulator. Alternatively, these substrates provided with elements may be used. Examples of the element provided for the substrate include a capacitor element, a resistor, a switching element, a light-emitting element, and a storage element.

(194) <<Insulator>>

(195) Examples of the insulator include an insulating oxide, an insulating nitride, an insulating oxynitride, an insulating nitride oxide, an insulating metal oxide, an insulating metal oxynitride, and an insulating metal nitride oxide.

(196) As miniaturization and high integration of transistors progress, for example, a problem such as a leakage current may arise because of a thinner gate insulator. When a high-k material is used for the insulator functioning as a gate insulator, the voltage during operation of the transistor can be lowered while the physical thickness of the gate insulator is maintained. In contrast, when a material with a low dielectric constant is used for the insulator functioning as an interlayer film, parasitic capacitance generated between wirings can be reduced. Thus, a material is preferably selected depending on the function of an insulator.

(197) Examples of the insulator with a high dielectric constant include gallium oxide, hafnium oxide, zirconium oxide, an oxide containing aluminum and hafnium, an oxynitride containing aluminum and hafnium, an oxide containing silicon and hafnium, an oxynitride containing silicon and hafnium, and a nitride containing silicon and hafnium.

(198) Examples of the insulator with a low dielectric constant include silicon oxide, silicon oxynitride, silicon nitride oxide, silicon nitride, silicon oxide to which fluorine is added, silicon oxide to which carbon is added, silicon oxide to which carbon and nitrogen are added, porous silicon oxide, and a resin.

(199) When a transistor using a metal oxide is surrounded by an insulator having a function of inhibiting passage of oxygen and impurities such as hydrogen, the transistor can have stable electrical characteristics. As the insulator having a function of inhibiting passage of oxygen and impurities such as hydrogen, a single layer or stacked layers of an insulator containing, for example, boron, carbon, nitrogen, oxygen, fluorine, magnesium, aluminum, silicon, phosphorus, chlorine, argon, gallium, germanium, yttrium, zirconium, lanthanum, neodymium, hafnium, or tantalum are used. Specifically, as the insulator having a function of inhibiting passage of oxygen and impurities such as hydrogen, a metal oxide such as aluminum oxide, magnesium oxide, gallium

oxide, germanium oxide, yttrium oxide, zirconium oxide, lanthanum oxide, neodymium oxide, hafnium oxide, or tantalum oxide; or a metal nitride such as aluminum nitride, silicon nitride oxide, or silicon nitride can be used.

(200) The insulator functioning as the gate insulator is preferably an insulator including a region containing oxygen released by heating. For example, when a structure is employed in which silicon oxide or silicon oxynitride including a region containing oxygen released by heating is in contact with the oxide **230**, oxygen vacancies included in the oxide **230** can be compensated for.

(201) <<Conductor>>

(202) As a conductor, it is preferable to use a metal element selected from aluminum, chromium, copper, silver, gold, platinum, tantalum, nickel, titanium, molybdenum, tungsten, hafnium, vanadium, niobium, manganese, magnesium, zirconium, beryllium, indium, ruthenium, iridium, strontium, lanthanum, and the like; an alloy containing any of the above metal elements; an alloy containing a combination of the above metal elements; or the like. For example, it is preferable to use tantalum nitride, titanium nitride, tungsten, a nitride containing titanium and aluminum, a nitride containing tantalum and aluminum, ruthenium oxide, ruthenium nitride, an oxide containing strontium and ruthenium, an oxide containing lanthanum and nickel, or the like. In addition, tantalum nitride, titanium nitride, a nitride containing titanium and aluminum, a nitride containing tantalum and aluminum, ruthenium oxide, ruthenium nitride, an oxide containing strontium and ruthenium, and an oxide containing lanthanum and nickel are preferable because they are oxidation-resistant conductive materials or materials that retain their conductivity even after absorbing oxygen. Alternatively, a semiconductor having high electrical conductivity, typified by polycrystalline silicon containing an impurity element such as phosphorus, or silicide such as nickel silicide may be used.

(203) A stack of a plurality of conductive layers formed of the above materials may be used. For example, a stacked-layer structure combining a material containing the above metal element and a conductive material containing oxygen may be employed. Alternatively, a stacked-layer structure combining a material containing the above metal element and a conductive material containing nitrogen may be employed. Alternatively, a stacked-layer structure combining a material containing the above metal element, a conductive material containing oxygen, and a conductive material containing nitrogen may be employed.

(204) In the case where an oxide is used for the channel formation region of the transistor, the conductor functioning as the gate electrode preferably employs a stacked-layer structure combining a material containing the above metal element and a conductive material containing oxygen. In this case, the conductive material containing oxygen is preferably provided on the channel formation region side. When the conductive material containing oxygen is provided on the channel formation region side, oxygen released from the conductive material is easily supplied to the channel formation region.

(205) For the conductor functioning as the gate electrode, it is particularly preferable to use a conductive material containing oxygen and a metal element contained in the metal oxide where the channel is formed. Alternatively, a conductive material containing the above metal element and nitrogen may be used. For example, a conductive material containing nitrogen, such as titanium nitride or tantalum nitride, may be used. Indium tin oxide, indium oxide containing tungsten oxide, indium zinc oxide containing tungsten oxide, indium oxide containing titanium oxide, indium tin oxide containing titanium oxide, indium zinc oxide, or indium tin oxide to which silicon is added may be used. Indium gallium zinc oxide containing nitrogen may be used. With the use of such a material, hydrogen contained in the metal oxide where the channel is formed can be captured in some cases. Alternatively, hydrogen entering from an external insulator or the like can be captured in some cases.

(206) <<Metal Oxide>>

(207) The oxide **230** is preferably formed using a metal oxide functioning as a semiconductor (an

oxide semiconductor). A metal oxide that can be used as the oxide **230** of the present invention is described below.

(208) The metal oxide preferably contains at least indium or zinc. In particular, indium and zinc are preferably contained. Furthermore, aluminum, gallium, yttrium, tin, or the like is preferably contained in addition to them. Furthermore, one kind or a plurality of kinds selected from boron, titanium, iron, nickel, germanium, zirconium, molybdenum, lanthanum, cerium, neodymium, hafnium, tantalum, tungsten, magnesium, cobalt, and the like may be contained.

(209) Here, the case where the metal oxide is an In-M-Zn oxide containing indium, the element M, and zinc is considered. The element M is aluminum, gallium, yttrium, or tin. Examples of other elements that can be used as the element M include boron, titanium, iron, nickel, germanium, zirconium, molybdenum, lanthanum, cerium, neodymium, hafnium, tantalum, tungsten, magnesium, and cobalt. Note that two or more of the above elements may be used in combination as the element M.

(210) Note that in this specification and the like, a metal oxide containing nitrogen is also collectively referred to as a metal oxide in some cases. A metal oxide containing nitrogen may be referred to as a metal oxynitride.

(211) <Classification of Crystal Structures>

(212) First, the classification of crystal structures of an oxide semiconductor is described with reference to FIG. 4A. FIG. 4A is a diagram showing the classification of crystal structures of an oxide semiconductor, typically IGZO (a metal oxide containing In, Ga, and Zn).

(213) As shown in FIG. 4A, an oxide semiconductor is roughly classified into “Amorphous”, “Crystalline”, and “Crystal”. “Amorphous” includes completely amorphous. “Crystalline” includes CAAC (c-axis-aligned crystalline), nc (nanocrystalline), and CAC (column-aligned composite) (excluding single crystal and poly crystal). Note that “Crystalline” excludes single crystal, poly crystal, and completely amorphous. “Crystal” includes single crystal and poly crystal.

(214) Note that the structures in the thick frame in FIG. 4A are in an intermediate state between “Amorphous” and “Crystal”, and belong to a new crystalline phase. That is, these structures are completely different from “Amorphous”, which is energetically unstable, and “Crystal”.

(215) A crystal structure of a film or a substrate can be evaluated with an X-Ray Diffraction (XRD) spectrum. FIG. 4B shows an XRD spectrum, which is obtained by GIXD (Grazing-Incidence XRD) measurement, of a CAAC-IGZO film classified into “Crystalline”. Note that a GIXD method is also referred to as a thin film method or a Seemann-Bohlin method. The XRD spectrum that is shown in FIG. 4B and obtained by GIXD measurement is hereinafter simply referred to as an XRD spectrum. The CAAC-IGZO film in FIG. 4B has a composition in the neighborhood of In:Ga:Zn=4:2:3 [atomic ratio]. The CAAC-IGZO film in FIG. 4B has a thickness of 500 nm.

(216) In FIG. 4B, the horizontal axis represents 2θ [deg.], and the vertical axis represents intensity [a.u.]. As shown in FIG. 4B, a clear peak indicating crystallinity is detected in the XRD spectrum of the CAAC-IGZO film. Specifically, a peak indicating c-axis alignment is detected at 2θ of around 31° in the XRD spectrum of the CAAC-IGZO film. As shown in FIG. 4B, the peak at 2θ of around 31° is asymmetric with respect to the axis of the angle at which the peak intensity is detected.

(217) A crystal structure of a film or a substrate can also be evaluated with a diffraction pattern obtained by a nanobeam electron diffraction (NBED) method (such a pattern is also referred to as a nanobeam electron diffraction pattern). FIG. 4C shows a diffraction pattern of the CAAC-IGZO film. FIG. 4C shows a diffraction pattern obtained by the NBED method in which an electron beam is incident in the direction parallel to the substrate. The CAAC-IGZO film in FIG. 4C has a composition in the neighborhood of In:Ga:Zn=4:2:3 [atomic ratio]. In the nanobeam electron diffraction method, electron diffraction is performed with a probe diameter of 1 nm.

(218) As shown in FIG. 4C, a plurality of spots indicating c-axis alignment are observed in the diffraction pattern of the CAAC-IGZO film.

(219) <<Structure of Oxide Semiconductor>>

(220) Oxide semiconductors might be classified in a manner different from that in FIG. 4A when classified in terms of the crystal structure. Oxide semiconductors are classified into a single crystal oxide semiconductor and a non-single-crystal oxide semiconductor, for example. Examples of the non-single-crystal oxide semiconductor include the above-described CAAC-OS and nc-OS. Other examples of the non-single-crystal oxide semiconductor include a polycrystalline oxide semiconductor, an amorphous-like oxide semiconductor (a-like OS), and an amorphous oxide semiconductor.

(221) Here, the above-described CAAC-OS, nc-OS, and a-like OS are described in detail.

(222) [CAAC-OS]

(223) The CAAC-OS is an oxide semiconductor that has a plurality of crystal regions each of which has c-axis alignment in a particular direction. Note that the particular direction refers to the film thickness direction of a CAAC-OS film, the normal direction of the surface where the CAAC-OS film is formed, or the normal direction of the surface of the CAAC-OS film. The crystal region refers to a region having a periodic atomic arrangement. When an atomic arrangement is regarded as a lattice arrangement, the crystal region also refers to a region with a uniform lattice arrangement. The CAAC-OS has a region where a plurality of crystal regions are connected in the a-b plane direction, and the region has distortion in some cases. Note that the distortion refers to a portion where the direction of a lattice arrangement changes between a region with a uniform lattice arrangement and another region with a uniform lattice arrangement in a region where a plurality of crystal regions are connected. That is, the CAAC-OS is an oxide semiconductor having c-axis alignment and having no clear alignment in the a-b plane direction.

(224) Note that each of the plurality of crystal regions is formed of one or more fine crystals (crystals each of which has a maximum diameter of less than 10 nm). In the case where the crystal region is formed of one fine crystal, the maximum diameter of the crystal region is less than 10 nm. In the case where the crystal region is formed of a large number of fine crystals, the size of the crystal region may be approximately several tens of nanometers.

(225) In the case of an In-M-Zn oxide (the element M is one or more kinds selected from aluminum, gallium, yttrium, tin, titanium, and the like), the CAAC-OS tends to have a layered crystal structure (also referred to as a layered structure) in which a layer containing indium (In) and oxygen (hereinafter, an In layer) and a layer containing the element M, zinc (Zn), and oxygen (hereinafter, an (M,Zn) layer) are stacked. Indium and the element M can be replaced with each other. Therefore, indium may be contained in the (M,Zn) layer. In addition, the element M may be contained in the In layer. Note that Zn may be contained in the In layer. Such a layered structure is observed as a lattice image in a high-resolution TEM image, for example.

(226) When the CAAC-OS film is subjected to structural analysis by out-of-plane XRD measurement with an XRD apparatus using $\theta/2\theta$ scanning, for example, a peak indicating c-axis alignment is detected at 2θ of 31° or around 31° . Note that the position of the peak indicating c-axis alignment (the value of 2θ) may change depending on the kind, composition, or the like of the metal element contained in the CAAC-OS.

(227) For example, a plurality of bright spots are observed in the electron diffraction pattern of the CAAC-OS film. Note that one spot and another spot are observed point-symmetrically with a spot of the incident electron beam passing through a sample (also referred to as a direct spot) as the symmetric center.

(228) When the crystal region is observed from the particular direction, a lattice arrangement in the crystal region is basically a hexagonal lattice arrangement; however, a unit lattice is not always a regular hexagon and is a non-regular hexagon in some cases. A pentagonal lattice arrangement, a heptagonal lattice arrangement, and the like are included in the distortion in some cases. Note that a clear crystal grain boundary (grain boundary) cannot be observed even in the vicinity of the distortion in the CAAC-OS. That is, formation of a crystal grain boundary is inhibited by the

distortion of lattice arrangement. This is probably because the CAAC-OS can tolerate distortion owing to a low density of arrangement of oxygen atoms in the a-b plane direction, an interatomic bond distance changed by substitution of a metal atom, and the like.

(229) A crystal structure in which a clear crystal grain boundary is observed is what is called polycrystal. It is highly probable that the crystal grain boundary becomes a recombination center and captures carriers and thus decreases the on-state current and field-effect mobility of a transistor, for example. Thus, the CAAC-OS in which no clear crystal grain boundary is observed is one of crystalline oxides having a crystal structure suitable for a semiconductor layer of a transistor. Note that Zn is preferably contained to form the CAAC-OS. For example, an In—Zn oxide and an In—Ga—Zn oxide are suitable because they can inhibit generation of a crystal grain boundary as compared with an In oxide.

(230) The CAAC-OS is an oxide semiconductor with high crystallinity in which no clear crystal grain boundary is observed. Thus, in the CAAC-OS, reduction in electron mobility due to the crystal grain boundary is less likely to occur. Moreover, since the crystallinity of an oxide semiconductor might be decreased by entry of impurities, formation of defects, or the like, the CAAC-OS can be regarded as an oxide semiconductor that has small amounts of impurities and defects (e.g., oxygen vacancies). Thus, an oxide semiconductor including the CAAC-OS is physically stable. Therefore, the oxide semiconductor including the CAAC-OS is resistant to heat and has high reliability. In addition, the CAAC-OS is stable with respect to high temperatures in the manufacturing process (what is called thermal budget). Accordingly, the use of the CAAC-OS for the OS transistor can extend the degree of freedom of the manufacturing process.

(231) [nc-OS]

(232) In the nc-OS, a microscopic region (e.g., a region with a size greater than or equal to 1 nm and less than or equal to 10 nm, in particular, a region with a size greater than or equal to 1 nm and less than or equal to 3 nm) has a periodic atomic arrangement. In other words, the nc-OS includes a fine crystal. Note that the size of the fine crystal is, for example, greater than or equal to 1 nm and less than or equal to 10 nm, particularly greater than or equal to 1 nm and less than or equal to 3 nm; thus, the fine crystal is also referred to as a nanocrystal. Furthermore, there is no regularity of crystal orientation between different nanocrystals in the nc-OS. Thus, the orientation in the whole film is not observed. Accordingly, the nc-OS cannot be distinguished from an a-like OS or an amorphous oxide semiconductor by some analysis methods. For example, when an nc-OS film is subjected to structural analysis using out-of-plane XRD measurement with an XRD apparatus using $\theta/2\theta$ scanning, a peak indicating crystallinity is not detected. Furthermore, a diffraction pattern like a halo pattern is observed when the nc-OS film is subjected to electron diffraction (also referred to as selected-area electron diffraction) using an electron beam with a probe diameter greater than the diameter of a nanocrystal (e.g., greater than or equal to 50 nm). Meanwhile, in some cases, a plurality of spots in a ring-like region with a direct spot as the center are observed in the obtained electron diffraction pattern when the nc-OS film is subjected to electron diffraction (also referred to as nanobeam electron diffraction) using an electron beam with a probe diameter nearly equal to or less than the diameter of a nanocrystal (e.g., greater than or equal to 1 nm and less than or equal to 30 nm).

(233) [a-Like OS]

(234) The a-like OS is an oxide semiconductor having a structure between those of the nc-OS and the amorphous oxide semiconductor. The a-like OS includes a void or a low-density region. That is, the a-like OS has low crystallinity as compared with the nc-OS and the CAAC-OS. Moreover, the a-like OS has higher hydrogen concentration in the film than the nc-OS and the CAAC-OS.

(235) <<Structure of Oxide Semiconductor>>

(236) Next, the above-described CAC-OS is described in detail. Note that the CAC-OS relates to the material composition.

(237) [CAC-OS]

(238) The CAC-OS refers to one composition of a material in which elements constituting a metal oxide are unevenly distributed with a size greater than or equal to 0.5 nm and less than or equal to 10 nm, preferably greater than or equal to 1 nm and less than or equal to 3 nm, or a similar size, for example. Note that a state in which one or more metal elements are unevenly distributed and regions including the metal element(s) are mixed with a size greater than or equal to 0.5 nm and less than or equal to 10 nm, preferably greater than or equal to 1 nm and less than or equal to 3 nm, or a similar size in a metal oxide is hereinafter referred to as a mosaic pattern or a patch-like pattern.

(239) In addition, the CAC-OS has a composition in which materials are separated into a first region and a second region to form a mosaic pattern, and the first regions are distributed in the film (this composition is hereinafter also referred to as a cloud-like composition). That is, the CAC-OS is a composite metal oxide having a composition in which the first regions and the second regions are mixed.

(240) Here, the atomic ratios of In, Ga, and Zn to the metal elements contained in the CAC-OS in an In—Ga—Zn oxide are denoted by [In], [Ga], and [Zn], respectively. For example, the first region in the CAC-OS in the In—Ga—Zn oxide has [In] higher than that in the composition of the CAC-OS film. Moreover, the second region has [Ga] higher than that in the composition of the CAC-OS film. For example, the first region has higher [In] than the second region and has lower [Ga] than the second region. Moreover, the second region has higher [Ga] than the first region and has lower [In] than the first region.

(241) Specifically, the first region includes indium oxide, indium zinc oxide, or the like as its main component. The second region includes gallium oxide, gallium zinc oxide, or the like as its main component. That is, the first region can be referred to as a region containing In as its main component. The second region can be referred to as a region containing Ga as its main component.

(242) Note that a clear boundary between the first region and the second region cannot be observed in some cases.

(243) For example, energy dispersive X-ray spectroscopy (EDX) is used to obtain EDX mapping, and according to the EDX mapping, the CAC-OS in the In—Ga—Zn oxide has a structure in which the region containing In as its main component (the first region) and the region containing Ga as its main component (the second region) are unevenly distributed and mixed.

(244) In the case where the CAC-OS is used for a transistor, a switching function (on/off switching function) can be given to the CAC-OS owing to the complementary action of the conductivity derived from the first region and the insulating property derived from the second region. That is, the CAC-OS has a conducting function in part of the material and has an insulating function in another part of the material; as a whole, the CAC-OS has a function of a semiconductor. Separation of the conducting function and the insulating function can maximize each function. Accordingly, when the CAC-OS is used for a transistor, high on-state current ($I_{\text{sub.on}}$), high field-effect mobility (μ), and excellent switching operation can be achieved.

(245) An oxide semiconductor has various structures with different properties. Two or more kinds among the amorphous oxide semiconductor, the polycrystalline oxide semiconductor, the a-like OS, the CAC-OS, the nc-OS, and the CAAC-OS may be included in the oxide semiconductor of one embodiment of the present invention.

(246) <Transistor Including Oxide Semiconductor>

(247) Next, the case where the above oxide semiconductor is used for a transistor is described.

(248) When the above oxide semiconductor is used for a transistor, a transistor with high field-effect mobility can be achieved. In addition, a transistor having high reliability can be achieved.

(249) An oxide semiconductor with a low carrier concentration is preferably used for a channel formation region of the transistor. For example, the carrier concentration in an oxide semiconductor in the channel formation region is lower than or equal to $1 \times 10^{17} \text{ cm}^{-3}$, preferably lower than or equal to $1 \times 10^{15} \text{ cm}^{-3}$, further preferably lower than or equal to 1×10^{13}

cm.sup.-3, still further preferably lower than or equal to 1×10^{11} cm.sup.-3, yet further preferably lower than 1×10^{10} cm.sup.-3, and higher than or equal to 1×10^{-9} cm.sup.-3. In order to reduce the carrier concentration in an oxide semiconductor film, the impurity concentration in the oxide semiconductor film is reduced so that the density of defect states can be reduced. In this specification and the like, a state with a low impurity concentration and a low density of defect states is referred to as a highly purified intrinsic or substantially highly purified intrinsic state. Note that an oxide semiconductor with a low carrier concentration may be referred to as a highly purified intrinsic or substantially highly purified intrinsic oxide semiconductor.

(250) A highly purified intrinsic or substantially highly purified intrinsic oxide semiconductor film has a low density of defect states and accordingly has a low density of trap states in some cases.

(251) Electric charge trapped by the trap states in the oxide semiconductor takes a long time to disappear and might behave like fixed electric charge. Thus, a transistor whose channel formation region is formed in an oxide semiconductor with a high density of trap states has unstable electrical characteristics in some cases.

(252) Accordingly, in order to obtain stable electrical characteristics of a transistor, reducing the impurity concentration in an oxide semiconductor is effective. In order to reduce the impurity concentration in the oxide semiconductor, it is preferable that the impurity concentration in an adjacent film be also reduced. Examples of impurities include hydrogen, nitrogen, an alkali metal, an alkaline earth metal, iron, nickel, and silicon.

(253) <Impurity>

(254) Here, the influence of each impurity in the oxide semiconductor is described.

(255) When silicon or carbon, which is one of Group 14 elements, is contained in the oxide semiconductor, defect states are formed in the oxide semiconductor. Thus, the concentration of silicon or carbon in the oxide semiconductor in the channel formation region and the concentration of silicon or carbon in the vicinity of an interface with the oxide semiconductor in the channel formation region (the concentrations obtained by SIMS) are each set lower than or equal to 2×10^{18} atoms/cm.³, preferably lower than or equal to 2×10^{17} atoms/cm.³.

(256) When the oxide semiconductor contains an alkali metal or an alkaline earth metal, defect states are formed and carriers are generated in some cases. Thus, a transistor using an oxide semiconductor that contains an alkali metal or an alkaline earth metal is likely to have normally-on characteristics. Thus, the concentration of an alkali metal or an alkaline earth metal in the oxide semiconductor in the channel formation region, which is obtained by SIMS, is lower than or equal to 1×10^{18} atoms/cm.³, preferably lower than or equal to 2×10^{16} atoms/cm.³.

(257) Furthermore, when the oxide semiconductor contains nitrogen, the oxide semiconductor easily becomes n-type by generation of electrons serving as carriers and an increase in carrier concentration. As a result, a transistor using an oxide semiconductor containing nitrogen as a semiconductor is likely to have normally-on characteristics. When nitrogen is contained in the oxide semiconductor, a trap state is sometimes formed. This might make the electrical characteristics of the transistor unstable. Therefore, the concentration of nitrogen in the oxide semiconductor in the channel formation region, which is obtained by SIMS, is set lower than or equal to 5×10^{19} atoms/cm.³, preferably lower than 5×10^{18} atoms/cm.³, further preferably lower than or equal to 1×10^{18} atoms/cm.³, still further preferably lower than or equal to 5×10^{17} atoms/cm.³.

(258) Hydrogen contained in the oxide semiconductor reacts with oxygen bonded to a metal atom to be water, and thus forms an oxygen vacancy in some cases. Entry of hydrogen into the oxygen vacancy generates an electron serving as a carrier in some cases. Furthermore, bonding of part of hydrogen to oxygen bonded to a metal atom causes generation of an electron serving as a carrier in some cases. Thus, a transistor using an oxide semiconductor containing hydrogen is likely to have normally-on characteristics. Accordingly, hydrogen in the oxide semiconductor in the channel formation region is preferably reduced as much as possible. Specifically, the hydrogen

concentration in the oxide semiconductor in the channel formation region, which is obtained by SIMS, is set lower than 1×10^{20} atoms/cm³, preferably lower than 5×10^{19} atoms/cm³, further preferably lower than 1×10^{19} atoms/cm³, still further preferably lower than 5×10^{18} atoms/cm³, yet still further preferably lower than 1×10^{18} atoms/cm³.

(259) When an oxide semiconductor with sufficiently reduced impurities is used for the channel formation region of the transistor, stable electrical characteristics can be given.

(260) <<Other Semiconductor Materials>>

(261) A semiconductor material that can be used for the oxide **230** is not limited to the above metal oxides. A semiconductor material that has a band gap (a semiconductor material that is not a zero-gap semiconductor) may be used for the oxide **230**. For example, a single element semiconductor such as silicon, a compound semiconductor such as gallium arsenide, or a layered material functioning as a semiconductor (also referred to as an atomic layer material or a two-dimensional material) is preferably used as a semiconductor material. In particular, a layered material functioning as a semiconductor is preferably used as a semiconductor material.

(262) Here, in this specification and the like, the layered material generally refers to a group of materials having a layered crystal structure. In the layered crystal structure, layers formed by covalent bonding or ionic bonding are stacked with bonding such as the Van der Waals force, which is weaker than covalent bonding or ionic bonding. The layered material has high electrical conductivity in a monolayer, that is, high two-dimensional electrical conductivity. When a material that functions as a semiconductor and has high two-dimensional electrical conductivity is used for a channel formation region, a transistor having a high on-state current can be provided.

(263) Examples of the layered material include graphene, silicene, and chalcogenide. Chalcogenide is a compound containing chalcogen. Chalcogen is a general term of elements belonging to Group 16, which includes oxygen, sulfur, selenium, tellurium, polonium, and livermorium. Examples of chalcogenide include transition metal chalcogenide and chalcogenide of Group 13 elements.

(264) For the oxide **230**, a transition metal chalcogenide functioning as a semiconductor is preferably used, for example. Specific examples of the transition metal chalcogenide which can be used for the oxide **230** include molybdenum sulfide (typically MoS₂), molybdenum selenide (typically MoSe₂), molybdenum telluride (typically MoTe₂), tungsten sulfide (typically WS₂), tungsten selenide (typically WSe₂), tungsten telluride (typically WTe₂), hafnium sulfide (typically HfS₂), hafnium selenide (typically HfSe₂), zirconium sulfide (typically ZrS₂), and zirconium selenide (typically ZrSe₂).

(265) <Manufacturing Method of Semiconductor Device>

(266) Next, a method for manufacturing the semiconductor device that is one embodiment of the present invention and is illustrated in FIG. 1A to FIG. 1D is described with reference to FIG. 7A to FIG. 22D.

(267) Note that A of each drawing is a top view. Moreover, B of each drawing is a cross-sectional view corresponding to a portion indicated by dashed-dotted line A1-A2 in A of each drawing, and is also a cross-sectional view in the channel length direction of the transistor **200**. Furthermore, C of each drawing is a cross-sectional view corresponding to a portion indicated by dashed-dotted line A3-A4 in A of each drawing, and is also a cross-sectional view in the channel width direction of the transistor **200**. Furthermore, D of each drawing is a cross-sectional view of a portion indicated by dashed-dotted line A5-A6 in A of each drawing. Note that for clarity of the drawing, some components are not illustrated in the top view of A of each drawing.

(268) Hereinafter, an insulating material for forming an insulator, a conductive material for forming a conductor, and a semiconductor material for forming a semiconductor can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like as appropriate.

(269) Examples of the sputtering method include an RF sputtering method in which a high-

frequency power source is used as a sputtering power source, a DC sputtering method in which a DC power source is used, and a pulsed DC sputtering method in which a voltage is applied while being changed in a pulsed manner. An RF sputtering method is mainly used in the case where an insulating film is deposited, and a DC sputtering method is mainly used in the case where a metal conductive film is deposited. The pulsed DC sputtering method is mainly used in the case where a compound such as an oxide, a nitride, or a carbide is deposited by a reactive sputtering method.

(270) Note that the CVD method can be classified into a plasma enhanced CVD (PECVD) method using plasma, a thermal CVD (TCVD) method using heat, a photo CVD method using light, and the like. Moreover, the CVD method can be classified into a metal CVD (MCVD) method and a metal organic CVD (MOCVD) method depending on a source gas to be used.

(271) A high-quality film can be obtained at a relatively low temperature by a plasma enhanced CVD method. Furthermore, a thermal CVD method is a deposition method that does not use plasma and thus enables less plasma damage to an object to be processed. For example, a wiring, an electrode, an element (a transistor, a capacitor, or the like), or the like included in a semiconductor device might be charged up by receiving electric charge from plasma. In that case, accumulated electric charge might break the wiring, the electrode, the element, or the like included in the semiconductor device. In contrast, such plasma damage does not occur in the case of a thermal CVD method, which does not use plasma, and thus the yield of the semiconductor device can be increased. In addition, a thermal CVD method does not cause plasma damage during deposition, so that a film with few defects can be obtained.

(272) As an ALD method, a thermal ALD method, in which a precursor and a reactant react with each other only by a thermal energy, a PEALD method, in which a reactant excited by plasma is used, and the like can be used.

(273) Unlike a deposition method in which particles ejected from a target or the like are deposited, a CVD method and an ALD method are deposition methods in which a film is formed by gas phase reaction at a surface of an object to be processed. Thus, a CVD method and an ALD method are deposition methods that enable favorable step coverage almost regardless of the shape of an object to be processed. In particular, an ALD method has excellent step coverage and excellent thickness uniformity and thus is suitable for covering a surface of an opening portion with a high aspect ratio, for example. On the other hand, an ALD method has a relatively low deposition rate, and thus is preferably used in combination with another deposition method with a high deposition rate, such as a CVD method, in some cases.

(274) By a CVD method, a film with a certain composition can be deposited depending on the flow rate ratio of the source gases. For example, by a CVD method, by changing the flow rate ratio of the source gases during the deposition, a film in which the composition is continuously changed can be deposited. In the case where the film is deposited while the flow rate ratio of the source gases is changed, as compared to the case where the film is deposited using a plurality of deposition chambers, the time taken for the deposition can be shortened because the time taken for transfer and pressure adjustment is omitted. Thus, the productivity of the semiconductor device can be increased in some cases.

(275) By an ALD method, a film with a certain composition can be deposited by concurrently introducing a plurality of precursors with different compositions or controlling the number of the introduction of each of the plurality of precursors with different compositions in one cycle.

(276) First, a substrate (not illustrated) is prepared, and the insulator **212** is deposited over the substrate (see FIG. 7A to FIG. 7D). The insulator **212** is preferably deposited by a sputtering method. By using a sputtering method that does not need to use hydrogen as a deposition gas, the hydrogen concentration in the insulator **212** can be reduced. Without limitation to a sputtering method, the insulator **212** may be deposited by a CVD method, an MBE method, a PLD method, an ALD method, or the like as appropriate.

(277) In this embodiment, for the insulator **212**, silicon nitride is deposited by a pulsed DC

sputtering method using a silicon target in an atmosphere containing a nitrogen gas. The use of the pulsed DC sputtering method can inhibit generation of particles due to arcing on the target surface, achieving more uniform film thickness. In addition, by using the pulsed voltage, rising and falling in discharge can be made steep as compared with the case where a high-frequency voltage is used. As a result, power can be supplied to an electrode more efficiently to improve the sputtering rate and film quality.

(278) The use of an insulator through which impurities such as water and hydrogen are less likely to pass, such as silicon nitride, can inhibit diffusion of impurities such as water and hydrogen contained in a layer below the insulator **212**. When an insulator through which copper is less likely to pass, such as silicon nitride, is used for the insulator **212**, even in the case where a metal that is likely to diffuse, such as copper, is used for a conductor in a layer (not illustrated) below the insulator **212**, upward diffusion of the metal through the insulator **212** can be inhibited.

(279) Next, the insulator **214** is deposited over the insulator **212** (see FIG. 7A to FIG. 7D). The insulator **214** is preferably deposited by a sputtering method. By using a sputtering method that does not need to use hydrogen as a deposition gas, the hydrogen concentration in the insulator **214** can be reduced. Without limitation to a sputtering method, the insulator **214** may be deposited by a CVD method, an MBE method, a PLD method, an ALD method, or the like as appropriate.

(280) In this embodiment, for the insulator **214**, aluminum oxide is deposited by a pulsed DC sputtering method using an aluminum target in an atmosphere containing an oxygen gas. The use of the pulsed DC sputtering method can achieve more uniform film thickness and improve the sputtering rate and film quality. Here, RF (Radio Frequency) power may be applied to the substrate. The amount of oxygen implanted to a layer below the insulator **214** can be controlled depending on the amount of the RF power applied to the substrate. The RF power is higher than or equal to 0 W/cm² and lower than or equal to 1.86 W/cm². In other words, the implantation amount of oxygen can be changed to be appropriate for the characteristics of the transistor, with the RF power used at the time of forming the insulator **214**. Accordingly, an appropriate amount of oxygen for improving the reliability of the transistor can be implanted. The RF frequency is preferably 10 MHz or higher. The typical frequency is 13.56 MHz. The higher the RF frequency is, the less damage the substrate gets.

(281) A metal oxide having an amorphous structure and an excellent function of capturing or fixing hydrogen, such as aluminum oxide, is preferably used for the insulator **214**. In this case, the insulator **214** captures or fixes hydrogen contained in the insulator **216** and the like and prevents the hydrogen from diffusing into the oxide **230**. It is particularly preferable to use aluminum oxide having an amorphous structure or amorphous aluminum oxide for the insulator **214** because hydrogen can be captured or fixed more effectively in some cases. Accordingly, the transistor **200** and a semiconductor device which have favorable characteristics and high reliability can be manufactured.

(282) Next, the insulator **216** is deposited over the insulator **214**. The insulator **216** is preferably deposited by a sputtering method. By using a sputtering method that does not need to use hydrogen as a deposition gas, the hydrogen concentration in the insulator **216** can be reduced. Without limitation to a sputtering method, the insulator **216** may be deposited by a CVD method, an MBE method, a PLD method, an ALD method, or the like as appropriate.

(283) In this embodiment, for the insulator **216**, silicon oxide is deposited by a pulsed DC sputtering method using a silicon target in an atmosphere containing an oxygen gas. The use of the pulsed DC sputtering method can achieve more uniform film thickness and improve the sputtering rate and film quality.

(284) The insulator **212**, the insulator **214**, and the insulator **216** are preferably successively deposited without exposure to the air. For example, a multi-chamber deposition apparatus is used. As a result, the amounts of hydrogen in the deposited insulator **212**, insulator **214**, and insulator **216** can be reduced, and furthermore, entry of hydrogen into the films in intervals between

deposition steps can be inhibited.

(285) Then, an opening reaching the insulator **214** is formed in the insulator **216**. Examples of the opening include a groove and a slit. A region where an opening is formed is referred to as an opening portion in some cases. Wet etching can be used for the formation of the opening; however, dry etching is preferably used for microfabrication. As the insulator **214**, it is preferable to select an insulator that functions as an etching stopper film used in forming the groove by etching the insulator **216**. For example, in the case where silicon oxide or silicon oxynitride is used for the insulator **216** in which the groove is to be formed, silicon nitride, aluminum oxide, or hafnium oxide is preferably used for the insulator **214**.

(286) As a dry etching apparatus, a capacitively coupled plasma (CCP) etching apparatus including parallel plate electrodes can be used. The capacitively coupled plasma etching apparatus including the parallel plate electrodes may have a structure in which a high-frequency voltage is applied to one of the parallel plate electrodes. Alternatively, a structure may be employed in which different high-frequency voltages are applied to one of the parallel plate electrodes. Alternatively, a structure may be employed in which high-frequency voltages with the same frequency are applied to the parallel plate electrodes. Alternatively, a structure may be employed in which high-frequency voltages with different frequencies are applied to the parallel plate electrodes. Alternatively, a dry etching apparatus including a high-density plasma source can be used. As the dry etching apparatus including a high-density plasma source, an inductively coupled plasma (ICP) etching apparatus or the like can be used, for example.

(287) After the formation of the opening, a conductive film **205A** is deposited (see FIG. 7A to FIG. 7D). The conductive film **205A** desirably includes a conductor having a function of inhibiting passage of oxygen. For example, tantalum nitride, tungsten nitride, or titanium nitride can be used. Alternatively, a stacked-layer film of the conductor having a function of inhibiting passage of oxygen and tantalum, tungsten, titanium, molybdenum, aluminum, copper, or a molybdenum-tungsten alloy can be used. The conductive film **205A** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like.

(288) In this embodiment, titanium nitride is deposited for the conductor film **205A**. When such a metal nitride is used for a layer under the conductor **205b**, oxidation of the conductor **205b** by the insulator **216** or the like can be inhibited. Furthermore, even when a metal that is likely to diffuse, such as copper, is used for the conductor **205b**, the metal can be prevented from diffusing to the outside through the conductor **205a**.

(289) Next, a conductive film **205B** is deposited (see FIG. 7A to FIG. 7D). Tantalum, tungsten, titanium, molybdenum, aluminum, copper, a molybdenum-tungsten alloy, or the like can be used for the conductive film **205B**. The conductive film **205B** can be deposited by a plating method, a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. In this embodiment, tungsten is deposited for the conductive film **205B**.

(290) Next, by performing CMP treatment, the conductive film **205A** and the conductive film **205B** are partly removed and the insulator **216** is exposed (see FIG. 8A to FIG. 8D). As a result, the conductor **205a** and the conductor **205b** remain only in the opening portion. Note that the insulator **216** is partly removed by the CMP treatment in some cases.

(291) Next, an upper portion of the conductor **205b** is removed by etching (see FIG. 9A to FIG. 9D). This makes the top surface of the conductor **205b** lower in level than the top surface of the conductor **205a** and the top surface of the insulator **216**. Dry etching or wet etching can be used for the etching of the conductor **205b**, and dry etching is preferably used for microfabrication.

(292) Next, a conductive film **205C** is deposited over the insulator **216**, the conductor **205a**, and the conductor **205b** (see FIG. 10A to FIG. 10D). Like the conductive film **205A**, the conductive film **205C** desirably includes a conductor having a function of inhibiting passage of oxygen.

(293) In this embodiment, titanium nitride is deposited for the conductive film **205C**. When such a metal nitride is used for a layer over the conductor **205b**, oxidation of the conductor **205b** by the

insulator **222** or the like can be inhibited. Furthermore, even when a metal that is likely to diffuse, such as copper, is used for the conductor **205b**, the metal can be prevented from diffusing to the outside through the conductor **205c**.

(294) Next, by performing CMP treatment, the conductive film **205C** is partly removed and the insulator **216** is exposed (see FIG. **11A** to FIG. **11D**). As a result, the conductor **205a**, the conductor **205b**, and the conductor **205c** remain only in the opening portion. In this way, the conductor **205** with a flat top surface can be formed. Furthermore, the conductor **205b** is surrounded by the conductor **205a** and the conductor **205c**. Thus, impurities such as hydrogen can be prevented from diffusing from the conductor **205b** to the outside of the conductor **205a** and the conductor **205c**, and the conductor **205b** can be prevented from being oxidized by oxygen entering from the outside of the conductor **205a** and the conductor **205c**. Note that the insulator **216** is partly removed by the CMP treatment in some cases.

(295) Next, the insulator **222** is deposited over the insulator **216** and the conductor **205**. An insulator containing an oxide of one or both of aluminum and hafnium is preferably deposited as the insulator **222**. Note that as the insulator containing an oxide of one or both of aluminum and hafnium, aluminum oxide, hafnium oxide, an oxide containing aluminum and hafnium (hafnium aluminate), or the like is preferably used. The insulator containing an oxide of one or both of aluminum and hafnium has a barrier property against oxygen, hydrogen, and water. When the insulator **222** has a barrier property against hydrogen and water, hydrogen and water contained in components provided around the transistor **200** are inhibited from diffusing into the transistor **200** through the insulator **222**, and generation of oxygen vacancies in the oxide **230** can be inhibited.

(296) The insulator **222** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. In this embodiment, for the insulator **222**, hafnium oxide is deposited by an ALD method.

(297) Sequentially, heat treatment is preferably performed. The heat treatment is performed at a temperature higher than or equal to 250° C. and lower than or equal to 650° C., preferably higher than or equal to 300° C. and lower than or equal to 500° C., further preferably higher than or equal to 320° C. and lower than or equal to 450° C. Note that the heat treatment is performed in a nitrogen gas or inert gas atmosphere, or an atmosphere containing an oxidizing gas at 10 ppm or more, 1% or more, or 10% or more. For example, in the case where the heat treatment is performed in a mixed atmosphere of a nitrogen gas and an oxygen gas, the proportion of the oxygen gas may be approximately 20%. The heat treatment may be performed under reduced pressure.

Alternatively, the heat treatment may be performed in such a manner that heat treatment is performed in a nitrogen gas or inert gas atmosphere, and then another heat treatment is performed in an atmosphere containing an oxidizing gas at 10 ppm or more, 1% or more, or 10% or more in order to compensate for released oxygen.

(298) The gas used in the above heat treatment is preferably highly purified. For example, the amount of moisture contained in the gas used in the above heat treatment is 1 ppb or less, preferably 0.1 ppb or less, further preferably 0.05 ppb or less. The heat treatment using a highly purified gas can prevent entry of moisture or the like into the insulator **222** and the like as much as possible.

(299) In this embodiment, as the heat treatment, treatment at 400° C. for one hour is performed with a flow rate ratio of a nitrogen gas and an oxygen gas of 4 slm:1 slm after the deposition of the insulator **222**. By the heat treatment, impurities such as water and hydrogen contained in the insulator **222** can be removed, for example. In the case where an oxide containing hafnium is used for the insulator **222**, the insulator **222** is partly crystallized by the heat treatment in some cases. The heat treatment can also be performed after the deposition of the insulator **224**, for example.

(300) Next, the insulator **224** is deposited over the insulator **222**. The insulator **224** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. In this embodiment, for the insulator **224**, silicon oxide is deposited by a

sputtering method. By using a sputtering method that does not need to use hydrogen as a deposition gas, the hydrogen concentration in the insulator **224** can be reduced. The hydrogen concentration in the insulator **224** is preferably reduced because the insulator **224** is in contact with the oxide **230a** in a later step.

(301) Next, an oxide film **230A** and an oxide film **230B** are deposited in this order over the insulator **224** (see FIG. **12A** to FIG. **12D**). Note that it is preferable to deposit the oxide film **230A** and the oxide film **230B** successively without exposure to the air. By the deposition without exposure to the air, impurities or moisture from the atmospheric environment can be prevented from being attached onto the oxide film **230A** and the oxide film **230B**, so that the vicinity of an interface between the oxide film **230A** and the oxide film **230B** can be kept clean.

(302) The oxide film **230A** and the oxide film **230B** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. An ALD method is preferably employed for the deposition of the oxide film **230A** and the oxide film **230B**, in which case a film with a uniform thickness can be formed even in a groove or an opening having a high aspect ratio. Employing a PEALD method is preferable because the oxide film **230A** and the oxide film **230B** can be formed at a lower temperature than the case of employing a thermal ALD method. In this embodiment, the oxide film **230A** and the oxide film **230B** are deposited by a sputtering method.

(303) For example, in the case where the oxide film **230A** and the oxide film **230B** are deposited by a sputtering method, oxygen or a mixed gas of oxygen and a rare gas is used as a sputtering gas. Increasing the proportion of oxygen contained in the sputtering gas can increase the amount of excess oxygen in the deposited oxide films. In the case where the oxide films are deposited by a sputtering method, the above In-M-Zn oxide target or the like can be used.

(304) In particular, when the oxide film **230A** is deposited, part of oxygen contained in the sputtering gas is supplied to the insulator **224** in some cases. Thus, the proportion of oxygen contained in the sputtering gas is higher than or equal to 70%, preferably higher than or equal to 80%, further preferably 100%.

(305) In the case where the oxide film **230B** is formed by a sputtering method and the proportion of oxygen contained in the sputtering gas for deposition is higher than 30% and lower than or equal to 100%, preferably higher than or equal to 70% and lower than or equal to 100%, an oxygen-excess oxide semiconductor is formed. In a transistor using an oxygen-excess oxide semiconductor for its channel formation region, relatively high reliability can be obtained. Note that one embodiment of the present invention is not limited thereto. In the case where the oxide film **230B** is formed by a sputtering method and the proportion of oxygen contained in the sputtering gas for deposition is higher than or equal to 1% and lower than or equal to 30%, preferably higher than or equal to 5% and lower than or equal to 20%, an oxygen-deficient oxide semiconductor is formed. In a transistor using an oxygen-deficient oxide semiconductor for its channel formation region, relatively high field-effect mobility can be obtained. Furthermore, when the deposition is performed while the substrate is being heated, the crystallinity of the oxide film can be improved.

(306) In this embodiment, the oxide film **230A** is deposited by a sputtering method using an oxide target with In:Ga:Zn=1:3:4 [atomic ratio]. In addition, the oxide film **230B** is deposited by a sputtering method using an oxide target with In:Ga:Zn=4:2:4.1 [atomic ratio], an oxide target with In:Ga:Zn=1:1:1 [atomic ratio], or an oxide target with In:Ga:Zn=1:1:0.5 [atomic ratio]. Note that each of the oxide films is preferably formed to have characteristics required for the oxide **230a** and the oxide **230b** by selecting the deposition conditions and the atomic ratios as appropriate.

(307) Next, an oxide film **243A** is deposited over the oxide film **230B** (see FIG. **12A** to FIG. **12D**). The oxide film **243A** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. The atomic ratio of Ga to In in the oxide film **243A** is preferably greater than the atomic ratio of Ga to In in the oxide film **230B**. In this embodiment, the oxide film **243A** is deposited by a sputtering method using an oxide target with In:Ga:Zn=1:3:4

[atomic ratio].

(308) Note that the insulator **222**, the insulator **224**, the oxide film **230A**, the oxide film **230B**, and the oxide film **243A** are preferably deposited by a sputtering method without exposure to the air. For example, a multi-chamber deposition apparatus is used. As a result, the amounts of hydrogen in the deposited insulator **222**, insulator **224**, oxide film **230A**, oxide film **230B**, and oxide film **243A** can be reduced, and furthermore, entry of hydrogen into the films in intervals between deposition steps can be inhibited.

(309) Next, heat treatment is preferably performed. The heat treatment is performed in a temperature range where the oxide film **230A**, the oxide film **230B**, and the oxide film **243A** do not become polycrystals, i.e., at a temperature higher than or equal to 250° C. and lower than or equal to 650° C., preferably higher than or equal to 400° C. and lower than or equal to 600° C. Note that the heat treatment is performed in a nitrogen gas or inert gas atmosphere, or an atmosphere containing an oxidizing gas at 10 ppm or more, 1% or more, or 10% or more. For example, in the case where the heat treatment is performed in a mixed atmosphere of a nitrogen gas and an oxygen gas, the proportion of the oxygen gas may be approximately 20%. The heat treatment may be performed under reduced pressure. Alternatively, the heat treatment may be performed in such a manner that heat treatment is performed in a nitrogen gas or inert gas atmosphere, and then another heat treatment is performed in an atmosphere containing an oxidizing gas at 10 ppm or more, 1% or more, or 10% or more in order to compensate for released oxygen.

(310) The gas used in the above heat treatment is preferably highly purified. For example, the amount of moisture contained in the gas used in the above heat treatment is 1 ppb or less, preferably 0.1 ppb or less, and further preferably 0.05 ppb or less. The heat treatment using a highly purified gas can prevent entry of moisture or the like into the oxide film **230A**, the oxide film **230B**, the oxide film **243A**, and the like as much as possible.

(311) In this embodiment, the heat treatment is performed in such a manner that treatment is performed at 400° C. in a nitrogen atmosphere for one hour and then another treatment is successively performed at 400° C. in an oxygen atmosphere for one hour. By the heat treatment, impurities such as water and hydrogen in the oxide film **230A**, the oxide film **230B**, and the oxide film **243A** can be removed, for example. Furthermore, the heat treatment improves the crystallinity of the oxide film **230B**, thereby offering a dense structure with higher density. Thus, diffusion of oxygen or impurities in the oxide film **230B** can be reduced.

(312) Next, a conductive film **242A** is deposited over the oxide film **243A** (see FIG. **12A** to FIG. **12D**). The conductive film **242A** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. For example, for the conductive film **242A**, tantalum nitride is deposited by a sputtering method. Note that heat treatment may be performed before the deposition of the conductive film **242A**. This heat treatment may be performed under reduced pressure, and the conductive film **242A** may be successively deposited without exposure to the air. The treatment can remove moisture and hydrogen adsorbed onto the surface of the oxide film **243A**, and further can reduce the moisture concentration and the hydrogen concentration in the oxide film **230A**, the oxide film **230B**, and the oxide film **243A**. The heat treatment is preferably performed at a temperature higher than or equal to 100° C. and lower than or equal to 400° C. In this embodiment, the heat treatment is performed at 200° C.

(313) Next, an insulating film **271A** is deposited over the conductive film **242A** (see FIG. **12A** to FIG. **12D**). The insulating film **271A** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. As the insulating film **271A**, an insulating film having a function of inhibiting passage of oxygen is preferably used. For example, for the insulating film **271A**, aluminum oxide or silicon nitride may be deposited by a sputtering method.

(314) In this embodiment, for the insulating film **271A**, aluminum oxide is deposited by a pulsed DC sputtering method using an aluminum target in an atmosphere containing an oxygen gas. The

RF power applied to the substrate is lower than or equal to 0.62 W/cm.^{sup.2}, preferably higher than or equal to 0 W/cm.^{sup.2} and lower than or equal to 0.31 W/cm.^{sup.2}. With low RF power, the amount of oxygen implanted to the conductive film **242A** can be reduced and oxidation of the conductive film **242A** can be prevented.

(315) Note that the conductive film **242A** and the insulating film **271A** are preferably deposited by a sputtering method without exposure to the air. For example, a multi-chamber deposition apparatus is used. As a result, the amounts of hydrogen in the conductive film **242A** and the insulating film **271A** can be reduced, and furthermore, entry of hydrogen into the films in intervals between deposition steps can be inhibited. In the case where a hard mask is provided over the insulating film **271A**, a film to be the hard mask is preferably successively formed without exposure to the air.

(316) Next, the oxide film **230A**, the oxide film **230B**, the oxide film **243A**, the conductive film **242A**, the insulating film **271A**, and the insulator **224** are processed into island shapes by a lithography method to form the oxide **230a**, the oxide **230b**, an oxide layer **243B**, a conductive layer **242B**, and an insulating layer **271B** (see FIG. **13A** to FIG. **13D**). A dry etching method or a wet etching method can be used for the processing. A dry etching method is suitable for microfabrication. The oxide film **230A**, the oxide film **230B**, the oxide film **243A**, the conductive film **242A**, the insulating film **271A**, and the insulator **224** may be processed under different conditions. In this step, the insulator **224** is processed into an island shape so as to overlap the oxide **230a**.

(317) Note that in the lithography method, first, a resist is exposed to light through a mask. Next, a region exposed to light is removed or left using a developing solution, so that a resist mask is formed. Then, etching process through the resist mask is conducted, whereby a conductor, a semiconductor, an insulator, or the like can be processed into a desired shape. The resist mask is formed through, for example, exposure of the resist to KrF excimer laser light, ArF excimer laser light, EUV (Extreme Ultraviolet) light, or the like. Alternatively, a liquid immersion technique may be employed in which a gap between a substrate and a projection lens is filled with liquid (e.g., water) in light exposure. Alternatively, an electron beam or an ion beam may be used instead of the light. Note that a mask is unnecessary in the case of using an electron beam or an ion beam. Note that the resist mask can be removed by dry etching process such as ashing, wet etching process, wet etching process after dry etching process, or dry etching process after wet etching process.

(318) In addition, a hard mask formed of an insulator or a conductor may be used under the resist mask. In the case of using a hard mask, a hard mask with a desired shape can be formed in the following manner: an insulating film or a conductive film that is the material of the hard mask is formed over the conductive film **242A**, a resist mask is formed thereover, and then the hard mask material is etched. The etching of the conductive film **242A** and the like may be performed after removing the resist mask or with the resist mask remaining. In the latter case, the resist mask sometimes disappears during the etching. The hard mask may be removed by etching after the etching of the conductive film **242A** and the like. Meanwhile, the hard mask is not necessarily removed when the hard mask material does not affect later steps or can be utilized in later steps. In this embodiment, in the case where the insulating layer **271B** is used as a hard mask, it is preferable to adjust the thickness of the insulating layer **271B** as appropriate in order to prevent the insulating layer **271B** from disappearing during the etching of the conductive film **242A** or the like.

(319) Here, the insulating layer **271B** functions as a mask for the conductive layer **242B**; thus, as illustrated in FIG. **13B** to FIG. **13D**, the conductive layer **242B** does not have a curved surface between the side surface and the top surface. Thus, end portions at the intersections of the side surfaces and the top surfaces of the conductor **242a** and the conductor **242b** illustrated in FIG. **1B** and FIG. **1D** are angular. The cross-sectional area of the conductor **242** is larger in the case where the end portion at the intersection of the side surface and the top surface of the conductor **242** is angular than in the case where the end portion is rounded. Accordingly, the resistance of the

conductor **242** is reduced, so that the on-state current of the transistor **200** can be increased.

(320) Here, the insulator **224**, the oxide **230a**, the oxide **230b**, the oxide layer **243B**, the conductive layer **242B**, and the insulating layer **271B** are formed to at least partly overlap the conductor **205**. It is preferable that the side surfaces of the insulator **224**, the oxide **230a**, the oxide **230b**, the oxide layer **243B**, the conductive layer **242B**, and the insulating layer **271B** be substantially perpendicular to the top surface of the insulator **222**. When the side surfaces of the insulator **224**, the oxide **230a**, the oxide **230b**, the oxide layer **243B**, the conductive layer **242B**, and the insulating layer **271B** are substantially perpendicular to the top surface of the insulator **222**, a plurality of transistors **200** can be provided in a smaller area and at a higher density. Alternatively, a structure may be employed in which an angle formed by the side surfaces of the insulator **224**, the oxide **230a**, the oxide **230b**, the oxide layer **243B**, the conductive layer **242B**, and the insulating layer **271B** and the top surface of the insulator **222** is a low angle. In that case, the angle formed by the side surfaces of the insulator **224**, the oxide **230a**, the oxide **230b**, the oxide layer **243B**, the conductive layer **242B**, and the insulating layer **271B** and the top surface of the insulator **222** is preferably greater than or equal to 60° and less than 70° . With such a shape, in later steps, the coverage with the insulator **272** and the like can be improved, so that defects such as a void can be reduced.

(321) A by-product generated in the etching process is sometimes formed in a layered manner on the side surfaces of the insulator **224**, the oxide **230a**, the oxide **230b**, the oxide layer **243B**, the conductive layer **242B**, and the insulating layer **271B**. In that case, the layered by-product is formed between the insulator **272** and each of the insulator **224**, the oxide **230a**, the oxide **230b**, the oxide **243**, the conductor **242**, and the insulating layer **271**. A layered by-product is also formed on the insulator **222** in some cases. When the manufacturing process of the transistor **200** proceeds in a state where the layered by-product is formed on the insulator **222**, the reliability of the transistor **200** might decrease. Hence, the layered by-product formed in contact with the top surface of the insulator **222** is preferably removed.

(322) Next, the insulator **272** is deposited over the insulator **224**, the oxide **230a**, the oxide **230b**, the oxide layer **243B**, the conductive layer **242B**, and the insulating layer **271B** (see FIG. **14A** to FIG. **14D**). The insulator **272** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. For the insulator **272**, silicon nitride, aluminum oxide, or the like can be used. The insulator **272** may have a stacked-layer structure. For example, silicon nitride may be deposited and then aluminum oxide may be deposited over the silicon nitride, or aluminum oxide may be deposited and then silicon nitride may be deposited over the aluminum oxide. In this embodiment, silicon nitride is deposited for the insulator **272** by a sputtering method.

(323) In this manner, the oxide **230a**, the oxide **230b**, the oxide layer **243B**, and the conductive layer **242B** can be covered with the insulator **272** and the insulating layer **271B**, which have a function of inhibiting diffusion of oxygen. This can inhibit diffusion of oxygen into the oxide **230a**, the oxide **230b**, the oxide layer **243B**, and the conductive layer **242B** in a later step.

(324) Next, an insulating film to be the insulator **280** is deposited over the insulator **272**. The insulating film can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. A silicon oxide film is deposited by a sputtering method as the insulating film, for example. When the insulating film is deposited by a sputtering method in an oxygen-containing atmosphere, the insulator **280** containing excess oxygen can be formed. Since hydrogen is not used as a deposition gas in the sputtering method, the concentration of hydrogen in the insulator **280** can be reduced. Note that heat treatment may be performed before the insulating film is deposited. The heat treatment may be performed under reduced pressure, and the insulating film may be successively deposited without exposure to the air. The treatment can remove moisture and hydrogen adsorbed onto the surface of the insulator **272** and the like, and further can reduce the moisture concentration and the hydrogen concentration in the oxide **230a**, the oxide **230b**, the

oxide layer **243B**, and the insulator **224**. For the heat treatment, the above heat treatment conditions can be used.

(325) Next, the insulating film to be the insulator **280** is subjected to CMP treatment, so that the insulator **280** with a flat top surface is formed (see FIG. **14A** to FIG. **14D**). Note that, for example, silicon nitride may be deposited over the insulator **280** by a sputtering method and CMP treatment may be performed on the silicon nitride until the insulator **280** is reached.

(326) Then, part of the insulator **280**, part of the insulator **272**, part of the insulating layer **271B**, part of the conductive layer **242B**, and part of the oxide layer **243B** are processed to form an opening reaching the oxide **230b**. The opening is preferably formed to overlap the conductor **205**. The insulator **271a**, the insulator **271b**, the conductor **242a**, the conductor **242b**, the oxide **243a**, and the oxide **243b** are formed through the formation of the opening (see FIG. **15A** to FIG. **15D**).

(327) An upper portion of the oxide **230b** is sometimes removed when the opening is formed. When part of the oxide **230b** is removed, a groove portion is formed in the oxide **230b**. The groove portion may be formed in the same step as the formation of the opening or in a step different from the formation of the opening in accordance with the depth of the groove portion.

(328) The part of the insulator **280**, the part of the insulator **272**, the part of the insulating layer **271B**, the part of the conductive layer **242B**, and the part of the oxide layer **243B** can be processed by a dry etching method or a wet etching method. A dry etching method is suitable for microfabrication. The processing may be performed under different conditions. For example, the part of the insulator **280** may be processed by a dry etching method, the part of the insulator **272** and the part of the insulating layer **271B** may be processed by a wet etching method, and the part of the conductive layer **242B** and the part of the oxide layer **243B** may be processed by a dry etching method. The part of the conductive layer **242B** and the part of the oxide layer **243B** may be processed under different conditions.

(329) Here, it is preferable to remove impurities that are attached onto the surfaces of the oxide **230a**, the oxide **230b**, and the like or diffused into the oxide **230a**, the oxide **230b**, and the like. It is also preferable to remove a damaged region that is formed on the surface of the oxide **230b** by the above dry etching. The impurities come from components contained in the insulator **280**, the insulator **272**, part of the insulating layer **271B**, and the conductive layer **242B**; components contained in a member of an apparatus used to form the opening; and components contained in a gas or a liquid used for etching, for instance. Examples of the impurities include aluminum, silicon, tantalum, fluorine, and chlorine.

(330) In particular, impurities such as aluminum and silicon hinder the oxide **230b** from becoming a CAAC-OS. It is thus preferable to reduce or remove impurity elements such as aluminum and silicon, which hinder the oxide from becoming a CAAC-OS. For example, the concentration of aluminum atoms in the oxide **230b** and in the vicinity thereof is lower than or equal to 5.0 atomic %, preferably lower than or equal to 2.0 atomic %, further preferably lower than or equal to 1.5 atomic %, still further preferably lower than or equal to 1.0 atomic %, and yet further preferably lower than 0.3 atomic %.

(331) Note that in a metal oxide, a region that is hindered from becoming a CAAC-OS by impurities such as aluminum and silicon and becomes an amorphous-like oxide semiconductor (a-like OS) is referred to as a non-CAAC region in some cases. In the non-CAAC region, the density of the crystal structure is reduced to increase V_{sub} ; thus, the transistor is likely to be normally on. Hence, the non-CAAC region in the oxide **230b** is preferably reduced or removed.

(332) In contrast, the oxide **230b** preferably has a layered CAAC structure. In particular, the CAAC structure preferably reaches a lower edge portion of a drain in the oxide **230b**. Here, in the transistor **200**, the conductor **242a** or the conductor **242b**, and its vicinity function as a drain. In other words, the oxide **230b** in the vicinity of the lower edge portion of the conductor **242a** (conductor **242b**) preferably has a CAAC structure. In this manner, the damaged region of the oxide **230b** is removed and the CAAC structure is formed in the edge portion of the drain, which

significantly affects the drain withstand voltage, so that variation in the electrical characteristics of the transistor **200** can be further suppressed. In addition, the reliability of the transistor **200** can be improved.

(333) In order to remove the above impurities and the like, cleaning treatment is performed. Examples of the cleaning method include wet cleaning using a cleaning solution, plasma treatment using plasma, and cleaning by heat treatment, and any of these cleanings may be performed in combination as appropriate. The cleaning treatment sometimes makes the groove portion deeper.

(334) As the wet cleaning, cleaning treatment may be performed using an aqueous solution in which ammonia water, oxalic acid, phosphoric acid, hydrofluoric acid, or the like is diluted with carbonated water or pure water; pure water; carbonated water; or the like. Alternatively, ultrasonic cleaning using such an aqueous solution, pure water, or carbonated water may be performed. Alternatively, such cleaning methods may be performed in combination as appropriate.

(335) Note that in this specification and the like, in some cases, an aqueous solution in which commercial hydrofluoric acid is diluted with pure water is referred to as diluted hydrofluoric acid, and an aqueous solution in which commercial ammonia water is diluted with pure water is referred to as diluted ammonia water. The concentration, temperature, and the like of the aqueous solution may be adjusted as appropriate in accordance with an impurity to be removed, the structure of a semiconductor device to be cleaned, or the like. The concentration of ammonia in the diluted ammonia water is higher than or equal to 0.01% and lower than or equal to 5%, preferably higher than or equal to 0.1% and lower than or equal to 0.5%. The concentration of hydrogen fluoride in the diluted hydrofluoric acid is higher than or equal to 0.01 ppm and lower than or equal to 100 ppm, preferably higher than or equal to 0.1 ppm and lower than or equal to 10 ppm.

(336) A frequency higher than or equal to 200 kHz, preferably higher than or equal to 900 kHz is used for the ultrasonic cleaning. Damage to the oxide **230b** and the like can be reduced with this frequency.

(337) The cleaning treatment may be performed a plurality of times, and the cleaning solution may be changed in every cleaning treatment. For example, the first cleaning treatment may use diluted hydrofluoric acid or diluted ammonia water and the second cleaning treatment may use pure water or carbonated water.

(338) As the cleaning treatment in this embodiment, wet cleaning using diluted hydrofluoric acid is performed, and then, wet cleaning using pure water or carbonated water is performed. The cleaning treatment can remove impurities that are attached onto the surfaces of the oxide **230a**, the oxide **230b**, and the like or diffused into the oxide **230a**, the oxide **230b**, and the like. Furthermore, the crystallinity of the oxide **230b** can be increased.

(339) By the processing such as dry etching or the cleaning treatment, the thickness of the insulator **224** in a region that is overlapped by the opening and is not overlapped by the oxide **230b** may become smaller than the thickness of the insulator **224** in a region that is overlapped by the oxide **230b**.

(340) After the etching or the cleaning treatment, heat treatment may be performed. The heat treatment is performed at higher than or equal to 100° C. and lower than or equal to 450° C., preferably higher than or equal to 350° C. and lower than or equal to 400° C. Note that the heat treatment is performed in a nitrogen gas or inert gas atmosphere, or an atmosphere containing an oxidizing gas at 10 ppm or more, 1% or more, or 10% or more. For example, the heat treatment is preferably performed in an oxygen atmosphere. Accordingly, oxygen can be supplied to the oxide **230a** and the oxide **230b** to reduce oxygen vacancies. In addition, the crystallinity of the oxide **230b** can be improved by the heat treatment. The heat treatment may be performed under reduced pressure. Alternatively, heat treatment may be performed in an oxygen atmosphere, and then heat treatment may be successively performed in a nitrogen atmosphere without exposure to the air.

(341) Next, an insulating film **250A** to be the insulator **250a** is deposited (see FIG. **16A** to FIG. **16D**). Heat treatment may be performed before the deposition of the insulating film **250A**; the heat

treatment may be performed under reduced pressure, and the insulating film **250A** may be successively deposited without exposure to the air. The heat treatment is preferably performed in an oxygen-containing atmosphere. Such treatment can remove moisture and hydrogen adsorbed onto the surface of the oxide **230b** and the like, and further can reduce the moisture concentration and the hydrogen concentration in the oxide **230a** and the oxide **230b**. The heat treatment is preferably performed at a temperature higher than or equal to 100° C. and lower than or equal to 400° C.

(342) The insulating film **250A** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. The insulating film **250A** is preferably deposited by a deposition method using a gas in which hydrogen atoms are reduced or removed. This can reduce the hydrogen concentration in the insulating film **250A**. The hydrogen concentration in the insulating film **250A** is preferably reduced because the insulating film **250A** becomes the insulator **250** that is in contact with the oxide **230b** in a later step.

(343) The insulating film **250A** is preferably deposited by a PEALD method using a gas (precursor) containing silicon but not containing hydrocarbon and an oxidizing gas (reactant). The thickness of the insulator **250**, which functions as a gate insulating film of the miniaturized transistor **200**, needs to be extremely small (e.g., approximately greater than or equal to 0.5 nm and less than or equal to 15.0 nm) and have a small variation. In contrast, a PEALD method is a deposition method in which a precursor and a reactant (oxidizer) are alternately introduced, and the film thickness can be adjusted with the number of repetition times of the sequence of the gas introduction; thus, accurate control of the film thickness is possible. Thus, the accuracy of the gate insulating film required by the miniaturized transistor **200** can be achieved. Furthermore, as illustrated in FIG. **16B** and FIG. **16C**, the insulating film **250A** needs to be deposited on the bottom surface and the side surface of the opening formed in the insulator **280** and the like so as to have good coverage. One atomic layer can be deposited at a time on the bottom surface and the side surface of the opening, whereby the insulating film **250A** can be deposited in the opening with good coverage. When a PEALD method is employed, deposition can be performed at a relatively low substrate temperature.

(344) When a gas (precursor) containing silicon but not containing hydrocarbon and an oxidizing gas (reactant) are used, entry of hydrogen into the insulating film **250A** and the oxide **230b** can be inhibited. Furthermore, a precursor containing an impurity such as carbon, e.g., an organic precursor having a CH group, is not used; thus, entry of hydrocarbon, an impurity such as carbon, or the like into the insulating film **250A** can be inhibited. In this manner, a denser film not containing an impurity or the like can be formed, and thus diffusion of In from the oxide **230b** into the insulating film **250A** can be prevented.

(345) In this embodiment, SiH₄ is used as a precursor, and N₂O is used as a reactant. For the deposition of the insulating film **250A**, according to the flow chart in FIG. **5** showing the process and the sequences shown in FIG. **6A** and FIG. **6B**, Step **S01** to Step **S04** are regarded as one cycle and repeated until a desired thickness is obtained.

(346) Next, an insulating film **250B** to be the insulator **250b** is deposited (see FIG. **17A** to FIG. **17D**). The insulating film **250B** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. The insulating film **250B** is preferably formed using an insulator having a function of inhibiting diffusion of oxygen. With such a structure, oxygen contained in the insulator **250a** can be inhibited from diffusing into the conductor **260**. That is, a reduction in the amount of oxygen supplied to the oxide **230** can be inhibited. In addition, oxidation of the conductor **260** due to oxygen contained in the insulator **250a** can be inhibited. For example, the insulating film **250A** can be formed using the above-described material that can be used for the insulator **250**, and the insulating film **250B** can be formed using a material similar to that for the insulator **222**.

(347) Specifically, for the insulating film **250B**, a metal oxide containing one kind or two or more kinds selected from hafnium, aluminum, gallium, yttrium, zirconium, tungsten, titanium, tantalum, nickel, germanium, magnesium, and the like, or a metal oxide that can be used for the oxide **230**

can be used. In particular, an insulator containing an oxide of one or both of aluminum and hafnium is preferably used.

(348) In this embodiment, silicon oxynitride is deposited for the insulating film **250A** by a PECVD method, and hafnium oxide is deposited for the insulating film **250B** by a thermal ALD method.

(349) Next, microwave treatment is performed in an oxygen-containing atmosphere (see FIG. **17A** to FIG. **17D**). Here, dotted lines shown in FIG. **17B**, FIG. **17C**, and FIG. **17D** indicate high-frequency waves such as microwaves or RF, oxygen plasma, oxygen radicals, or the like. For the microwave treatment, a microwave treatment apparatus including a power source for generating high-density plasma using a microwave is preferably used, for example. The microwave treatment apparatus may include a power source for applying RF to the substrate side. The use of high-density plasma enables high-density oxygen radicals to be generated. Furthermore, application of RF to the substrate side allows oxygen ions generated by the high-density plasma to be efficiently introduced into the oxide **230b**. The microwave treatment is preferably performed under reduced pressure, and the pressure is set to 60 Pa or higher, preferably 133 Pa or higher, further preferably 200 Pa or higher, still further preferably 400 Pa or higher. Furthermore, the oxygen flow rate ratio ($(O_{sub.2}/(O_{sub.2}+Ar))$) is lower than or equal to 50%, preferably higher than or equal to 10% and lower than or equal to 30%. The treatment temperature is lower than or equal to 750° C., preferably lower than or equal to 500° C., and is approximately 400° C., for example. After the oxygen plasma treatment, heat treatment may be successively performed without exposure to the air.

(350) As illustrated in FIG. **17B**, FIG. **17C**, and FIG. **17D**, the microwave treatment in an oxygen-containing atmosphere can convert an oxygen gas into plasma using a high-frequency wave such as a microwave or RF, and apply the oxygen plasma to a region of the oxide **230b** which is between the conductor **242a** and the conductor **242b**. At this time, the region **230bc** can also be irradiated with the high-frequency wave such as the microwave or RF. In other words, the high-frequency wave such as the microwave or RF, the oxygen plasma, or the like can be applied to the region **230bc** in FIG. **3**. The effect of the plasma, the microwave, or the like enables V.sub.OH in the region **230bc** to be cut, and hydrogen to be removed from the region **230bc**. That is, the reaction “V.sub.OH.fwdarw.H+V.sub.O” occurs in the region **230bc**, so that the concentration of hydrogen in the region **230bc** can be reduced. As a result, oxygen vacancies and V.sub.OH in the region **230bc** can be reduced to lower the carrier concentration. In addition, oxygen radicals generated by the oxygen plasma or oxygen contained in the insulator **250** can be supplied to oxygen vacancies formed in the region **230bc**, thereby further reducing oxygen vacancies and lowering the carrier concentration in the region **230bc**.

(351) Meanwhile, the conductor **242a** and the conductor **242b** are provided over the region **230ba** and the region **230bb** illustrated in FIG. **3**. As illustrated in FIG. **17B**, FIG. **17C**, and FIG. **17D**, the effect of the high-frequency wave such as the microwave or RF, the oxygen plasma, or the like is blocked by the conductor **242a** and the conductor **242b**, and thus does not reach the region **230ba** and the region **230bb**. Hence, a reduction in V.sub.OH and supply of an excess amount of oxygen due to the microwave treatment do not occur in the region **230ba** and the region **230bb**, preventing a decrease in carrier concentration.

(352) In the above manner, oxygen vacancies and V.sub.OH can be selectively removed from the region **230bc** in the oxide semiconductor, whereby the region **230bc** can be an i-type or substantially i-type region. Furthermore, supply of an excess amount of oxygen to the region **230ba** and the region **230bb** functioning as the source region and the drain region can be inhibited and the n-type regions can be maintained. As a result, a change in the electrical characteristics of the transistor **200** can be inhibited, and thus a variation in the electrical characteristics of the transistors **200** in the substrate plane can be inhibited.

(353) Thus, a semiconductor device with a small variation in transistor characteristics can be provided. A semiconductor device having favorable reliability can be provided. A semiconductor device having favorable electrical characteristics can be provided.

(354) After the insulating film **250A** is deposited, microwave treatment may be performed. Alternatively, microwave treatment may be performed after the deposition of the insulating film **250A**, and microwave treatment is not necessarily performed after the deposition of the insulating film **250B**.

(355) Heat treatment with the reduced pressure being maintained may be performed after each of microwave treatment after the deposition of the insulating film **250A** and microwave treatment after the deposition of the insulating film **250B**. Such treatment enables hydrogen in the insulating film **250A**, the insulating film **250B**, the oxide **230b**, and the oxide **230a** to be removed efficiently. Part of hydrogen is gettered by the conductor **242** (the conductor **242a** and the conductor **242b**) in some cases. Alternatively, the step of performing microwave treatment and then performing heat treatment with the reduced pressure being maintained may be repeated a plurality of cycles. The repetition of the heat treatment enables hydrogen in the insulating film **250A**, the oxide **230b**, and the oxide **230a** to be removed more efficiently. Note that the temperature of the heat treatment is preferably higher than or equal to 300° C. and lower than or equal to 500° C.

(356) Furthermore, the microwave treatment improves the film quality of the insulating film **250A** and the insulating film **250B**, thereby inhibiting diffusion of hydrogen, water, impurities, and the like. Accordingly, hydrogen, water, impurities, and the like can be inhibited from diffusing into the oxide **230b**, the oxide **230a**, and the like through the insulator **250** in a later step such as deposition of a conductive film to be the conductor **260** or later treatment such as heat treatment.

(357) Next, a conductive film to be the conductor **260a** and a conductive film to be the conductor **260b** are deposited in this order. The conductive film to be the conductor **260a** and the conductive film to be the conductor **260b** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. In this embodiment, the conductive film to be the conductor **260a** is deposited by an ALD method, and the conductive film to be the conductor **260b** is deposited by a CVD method.

(358) Then, the insulating film **250A**, the insulating film **250B**, the conductive film to be the conductor **260a**, and the conductive film to be the conductor **260b** are polished by CMP treatment until the insulator **280** is exposed, whereby the insulator **250a**, the insulator **250b**, and the conductor **260** (the conductor **260a** and the conductor **260b**) are formed (see FIG. **18A** to FIG. **18D**). Accordingly, the insulator **250** is placed to cover the inner wall (the side wall and the bottom surface) of the opening reaching the oxide **230b** and the groove portion of the oxide **230b**. The conductor **260** is placed to fill the opening and the groove portion with the insulator **250** therebetween.

(359) Then, heat treatment may be performed under conditions similar to those for the above heat treatment. In this embodiment, treatment is performed at 400° C. in a nitrogen atmosphere for one hour. The heat treatment can reduce the moisture concentration and the hydrogen concentration in the insulator **250** and the insulator **280**. After the heat treatment, the insulator **282** may be deposited successively without exposure to the air.

(360) Next, the insulator **282a** and the insulator **282b** are successively formed over the insulator **250**, the conductor **260**, and the insulator **280** (see FIG. **19A** to FIG. **19D**). The insulator **282a** and the insulator **282b** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. The insulator **282a** and the insulator **282b** are preferably deposited by a sputtering method. Since hydrogen is not used as a deposition gas in the sputtering method, the hydrogen concentrations in the insulator **282a** and the insulator **282b** can be reduced.

(361) In this embodiment, for the insulator **282a** and the insulator **282b**, aluminum oxide is deposited by a pulsed DC sputtering method using an aluminum target in an atmosphere containing an oxygen gas. The use of the pulsed DC sputtering method can achieve more uniform film thickness and improve the sputtering rate and film quality. The RF power applied to the substrate is lower than or equal to 1.86 W/cm.^{sup.2}, preferably higher than or equal to 0 W/cm.^{sup.2} and lower than or equal to 0.31 W/cm.^{sup.2}. With low RF power, the amount of oxygen implanted into the

insulator **280** can be reduced. In this embodiment, the insulator **282a** is deposited with the RF power applied to the substrate of 0 W/cm.sup.2, and the insulator **282b** is deposited with the RF power applied to the substrate of 0.31 W/cm.sup.2.

(362) Next, the insulator **282a**, the insulator **282b**, the insulator **280**, the insulator **272**, the insulator **222**, and the insulator **216** are processed until the top surface of the insulator **214** is reached (see FIG. **20A** to FIG. **20D**). Wet etching can be used for the processing; however, dry etching is preferably used for microfabrication.

(363) Next, heat treatment may be performed. The heat treatment is performed at higher than or equal to 250° C. and lower than or equal to 650° C., preferably higher than or equal to 400° C. and lower than or equal to 600° C. The heat treatment is preferably performed at a temperature lower than that of the heat treatment performed after the deposition of the oxide film **243A**. Note that the heat treatment is performed in an atmosphere of a nitrogen gas or an inert gas. By the heat treatment, oxygen contained in the insulator **280** and hydrogen bonded to the oxygen can be released to the outside from the side surface of the insulator **280** formed by the processing of the insulator **282a**, the insulator **282b**, the insulator **280**, the insulator **272**, the insulator **222**, and the insulator **216**. Moreover, oxygen contained in the insulator **280** and hydrogen bonded to the oxygen can be released to the outside. Note that the hydrogen bonded to oxygen is released as water. Thus, unnecessary oxygen and hydrogen contained in the insulator **280** can be reduced.

(364) Next, the insulator **283** is formed over the insulator **282b** (see FIG. **21A** to FIG. **21D**). The insulator **283** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. The insulator **283** is preferably deposited by a sputtering method. By using a sputtering method that does not need to use hydrogen as a deposition gas, the hydrogen concentration in the insulator **283** can be reduced. The insulator **283** may be a multilayer. For example, silicon nitride may be deposited by a sputtering method and silicon nitride may be deposited over the silicon nitride by an ALD method. Surrounding the transistor **200** by the insulator **283** and the insulator **214** having high barrier properties can prevent entry of moisture and hydrogen from the outside.

(365) Next, the insulator **274** is formed over the insulator **283**. The insulator **274** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. In this embodiment, for the insulator **274**, silicon oxide is deposited by a CVD method.

(366) Next, the insulator **274** is polished by CMP treatment until the insulator **283** is exposed, whereby a top surface of the insulator **274** is planarized (see FIG. **22A** to FIG. **22D**). The top surface of the insulator **283** is partly removed by the CMP treatment in some cases.

(367) Next, the insulator **284** is formed over the insulator **274** and the insulator **283** (see FIG. **22A** to FIG. **22D**). The insulator **284** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. The insulator **284** is preferably deposited by a sputtering method. By using a sputtering method that does not need to use hydrogen as a deposition gas, the hydrogen concentration in the insulator **284** can be reduced.

(368) In this embodiment, for the insulator **284**, aluminum oxide is deposited by a pulsed DC sputtering method using an aluminum target in an atmosphere containing an oxygen gas. The use of the pulsed DC sputtering method can achieve more uniform film thickness and improve the sputtering rate and film quality. The RF power applied to the substrate is lower than or equal to 0.62 W/cm.sup.2, preferably higher than or equal to 0 W/cm.sup.2 and lower than or equal to 0.31 W/cm.sup.2. In addition, the RF power applied to the substrate is preferably higher than the RF power applied to the substrate in depositing the insulator **282**.

(369) Subsequently, openings reaching the conductor **242** are formed in the insulator **271**, the insulator **272**, the insulator **280**, the insulator **282**, the insulator **283**, and the insulator **284** (see FIG. **22A** and FIG. **22B**). The openings are formed by a lithography method. Note that the openings in the top view in FIG. **22A** each have a circular shape; however, the shapes of the openings are not limited thereto. For example, the openings in the top view may each have an almost circular shape

such as an elliptical shape, a polygonal shape such as a quadrangular shape, or a polygonal shape such as a quadrangular shape with rounded corners.

(370) Subsequently, an insulating film to be the insulator **241** is deposited and the insulating film is subjected to anisotropic etching, so that the insulator **241** is formed (see FIG. **22B**). The insulating film can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. As the insulating film, an insulating film having a function of inhibiting passage of oxygen is preferably used. For example, aluminum oxide is preferably deposited by an ALD method. Alternatively, silicon nitride is preferably deposited by a PEALD method. Silicon nitride is preferable because it has a high blocking property against hydrogen.

(371) As an anisotropic etching for the insulating film to be the insulator **241**, a dry etching method may be employed, for example. When the insulator **241** is provided on the sidewall portions of the openings, passage of oxygen from the outside can be inhibited and oxidation of the conductor **240a** and the conductor **240b** to be formed next can be prevented. Furthermore, impurities such as water and hydrogen can be prevented from diffusing from the conductor **240a** and the conductor **240b** to the outside.

(372) Next, a conductive film to be the conductor **240a** and the conductor **240b** is deposited. The conductive film desirably has a stacked-layer structure which includes a conductor having a function of inhibiting passage of impurities such as water and hydrogen. For example, a stacked layer of tantalum nitride, titanium nitride, or the like and tungsten, molybdenum, copper, or the like can be employed. The conductive film can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like.

(373) Then, part of the conductive film to be the conductor **240a** and the conductor **240b** is removed by CMP treatment to expose the top surface of the insulator **284**. As a result, the conductive film remains only in the openings, so that the conductor **240a** and the conductor **240b** having flat top surfaces can be formed (see FIG. **22B**). Note that the top surface of the insulator **284** is partly removed by the CMP treatment in some cases.

(374) Next, a conductive film to be the conductor **246** is deposited. The conductive film can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like.

(375) Then, the conductive film to be the conductor **246** is processed by a lithography method, thereby forming the conductor **246a** in contact with the top surface of the conductor **240a** and the conductor **246b** in contact with the top surface of the conductor **240b**. At this time, part of the insulator **284** in a region where the insulator **284** does not overlap the conductor **246a** and the conductor **246b** is sometimes removed.

(376) Next, the insulator **286** is deposited over the conductor **246** and the insulator **284**. The insulator **286** can be deposited by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. In addition, the insulator **286** may have a multilayer structure. For example, silicon nitride may be deposited by a sputtering method and silicon nitride may be deposited by a CVD method over the silicon nitride.

(377) Through the above process, the semiconductor device including the transistor **200** illustrated in FIG. **1A** to FIG. **1D** can be manufactured. As illustrated in FIG. **7A** to FIG. **22D**, the transistor **200** can be manufactured with the use of the method for manufacturing the semiconductor device described in this embodiment.

(378) <Microwave Treatment Apparatus>

(379) A microwave treatment apparatus that can be used for the above method for manufacturing the semiconductor device is described below.

(380) First, a structure of a manufacturing apparatus that hardly allows entry of impurities in manufacturing a semiconductor device or the like is described with reference to FIG. **23** to FIG. **26**.

(381) FIG. **23** schematically illustrates a top view of a single wafer multi-chamber manufacturing apparatus **2700**. The manufacturing apparatus **2700** includes an atmosphere-side substrate supply

chamber **2701** including a cassette port **2761** for storing substrates and an alignment port **2762** for performing alignment of substrates; an atmosphere-side substrate transfer chamber **2702** through which a substrate is transferred from the atmosphere-side substrate supply chamber **2701**; a load lock chamber **2703a** where a substrate is carried in and the pressure inside the chamber is switched from atmospheric pressure to reduced pressure or from reduced pressure to atmospheric pressure; an unload lock chamber **2703b** where a substrate is carried out and the pressure inside the chamber is switched from reduced pressure to atmospheric pressure or from atmospheric pressure to reduced pressure; a transfer chamber **2704** through which a substrate is transferred in a vacuum; a chamber **2706a**; a chamber **2706b**; a chamber **2706c**; and a chamber **2706d**.

(382) Furthermore, the atmosphere-side substrate transfer chamber **2702** is connected to the load lock chamber **2703a** and the unload lock chamber **2703b**, the load lock chamber **2703a** and the unload lock chamber **2703b** are connected to the transfer chamber **2704**, and the transfer chamber **2704** is connected to the chamber **2706a**, the chamber **2706b**, the chamber **2706c**, and the chamber **2706d**.

(383) Note that gate valves GV are provided in connecting portions between the chambers so that each chamber excluding the atmosphere-side substrate supply chamber **2701** and the atmosphere-side substrate transfer chamber **2702** can be independently kept in a vacuum state. Furthermore, the atmosphere-side substrate transfer chamber **2702** is provided with a transfer robot **2763a**, and the transfer chamber **2704** is provided with a transfer robot **2763b**. With the transfer robot **2763a** and the transfer robot **2763b**, a substrate can be transferred inside the manufacturing apparatus **2700**.

(384) The back pressure (total pressure) in the transfer chamber **2704** and each of the chambers is, for example, lower than or equal to 1×10^{-4} Pa, preferably lower than or equal to 3×10^{-5} Pa, further preferably lower than or equal to 1×10^{-5} Pa. Furthermore, the partial pressure of a gas molecule (atom) having a mass-to-charge ratio (m/z) of 18 in the transfer chamber **2704** and each of the chambers is, for example, lower than or equal to 3×10^{-5} Pa, preferably lower than or equal to 1×10^{-5} Pa, further preferably lower than or equal to 3×10^{-6} Pa. Furthermore, the partial pressure of a gas molecule (atom) having m/z of 28 in the transfer chamber **2704** and each of the chambers is, for example, lower than or equal to 3×10^{-5} Pa, preferably lower than or equal to 1×10^{-5} Pa, further preferably lower than or equal to 3×10^{-6} Pa. Furthermore, the partial pressure of a gas molecule (atom) having m/z of 44 in the transfer chamber **2704** and each of the chambers is, for example, lower than or equal to 3×10^{-5} Pa, preferably lower than or equal to 1×10^{-5} Pa, further preferably lower than or equal to 3×10^{-6} Pa.

(385) Note that the total pressure and the partial pressure in the transfer chamber **2704** and each of the chambers can be measured using a mass analyzer. For example, Qulee CGM-051, a quadrupole mass analyzer (also referred to as Q-mass) produced by ULVAC, Inc. can be used.

(386) Furthermore, the transfer chamber **2704** and the chambers each desirably have a structure in which the amount of external leakage or internal leakage is small. For example, the leakage rate in the transfer chamber **2704** and each of the chambers is less than or equal to 3×10^{-6} Pa.Math.m.sup.3/s, preferably less than or equal to 1×10^{-6} Pa.Math.m.sup.3/s. Furthermore, for example, the leakage rate of a gas molecule (atom) having m/z of 18 is less than or equal to 1×10^{-7} Pa.Math.m.sup.3/s, preferably less than or equal to 3×10^{-8} Pa.Math.m.sup.3/s. Furthermore, for example, the leakage rate of a gas molecule (atom) having m/z of 28 is less than or equal to 1×10^{-5} Pa.Math.m.sup.3/s, preferably less than or equal to 1×10^{-6} Pa.Math.m.sup.3/s. Furthermore, for example, the leakage rate of a gas molecule (atom) having m/z of 44 is less than or equal to 3×10^{-6} Pa.Math.m.sup.3/s, preferably less than or equal to 1×10^{-6} Pa.Math.m.sup.3/s.

(387) Note that a leakage rate can be derived from the total pressure and partial pressure measured using the above-described mass analyzer. The leakage rate depends on external leakage and internal leakage. The external leakage refers to inflow of gas from the outside of a vacuum system through a minute hole, a sealing defect, or the like. The internal leakage is due to leakage through a

partition, such as a valve, in a vacuum system or released gas from an internal member. Measures need to be taken from both aspects of external leakage and internal leakage in order that the leakage rate can be set to less than or equal to the above-described value.

(388) For example, open/close portions of the transfer chamber **2704** and each of the chambers are preferably sealed with a metal gasket. For the metal gasket, metal covered with iron fluoride, aluminum oxide, or chromium oxide is preferably used. The metal gasket achieves higher adhesion than an O-ring and can reduce the external leakage. Furthermore, with the use of the metal covered with iron fluoride, aluminum oxide, chromium oxide, or the like, which is in the passive state, the release of gas containing impurities released from the metal gasket is inhibited, so that the internal leakage can be reduced.

(389) Furthermore, for a member of the manufacturing apparatus **2700**, aluminum, chromium, titanium, zirconium, nickel, or vanadium, which releases a small amount of gas containing impurities, is used. Furthermore, an alloy containing iron, chromium, nickel, and the like covered with the above-described metal, which releases a small amount of gas containing impurities, may be used. The alloy containing iron, chromium, nickel, and the like is rigid, resistant to heat, and suitable for processing. Here, when surface unevenness of the member is reduced by polishing or the like to reduce the surface area, the release of gas can be reduced.

(390) Alternatively, the above-described member of the manufacturing apparatus **2700** may be covered with iron fluoride, aluminum oxide, chromium oxide, or the like.

(391) The member of the manufacturing apparatus **2700** is preferably formed using only metal when possible, and in the case where a viewing window formed of quartz or the like is provided, for example, the surface is preferably thinly covered with iron fluoride, aluminum oxide, chromium oxide, or the like to inhibit release of gas.

(392) An adsorbed substance present in the transfer chamber **2704** and each of the chambers does not affect the pressure in the transfer chamber **2704** and each of the chambers because it is adsorbed onto an inner wall or the like; however, it causes a release of gas when the transfer chamber **2704** and each of the chambers are evacuated. Thus, although there is no correlation between the leakage rate and the exhaust rate, it is important that the adsorbed substance present in the transfer chamber **2704** and each of the chambers be desorbed as much as possible and exhaust be performed in advance with the use of a pump having high exhaust capability. Note that the transfer chamber **2704** and each of the chambers may be subjected to baking to promote desorption of the adsorbed substance. By the baking, the desorption rate of the adsorbed substance can be increased about tenfold. The baking is performed at higher than or equal to 100° C. and lower than or equal to 450° C. At this time, when the adsorbed substance is removed while an inert gas is introduced into the transfer chamber **2704** and each of the chambers, the desorption rate of water or the like, which is difficult to desorb simply by exhaust, can be further increased. Note that when the inert gas to be introduced is heated to substantially the same temperature as the baking temperature, the desorption rate of the adsorbed substance can be further increased. Here, a rare gas is preferably used as the inert gas.

(393) Alternatively, treatment for evacuating the transfer chamber **2704** and each of the chambers is preferably performed a certain period of time after a heated inert gas such as a rare gas, heated oxygen, or the like is introduced to increase the pressure in the transfer chamber **2704** and each of the chambers. The introduction of the heated gas can desorb the adsorbed substance in the transfer chamber **2704** and each of the chambers, and impurities present in the transfer chamber **2704** and each of the chambers can be reduced. Note that this treatment is effective when repeated more than or equal to 2 times and less than or equal to 30 times, preferably more than or equal to 5 times and less than or equal to 15 times. Specifically, an inert gas, oxygen, or the like at a temperature higher than or equal to 40° C. and lower than or equal to 400° C., preferably higher than or equal to 50° C. and lower than or equal to 200° C. is introduced, so that the pressure in the transfer chamber **2704** and each of the chambers can be kept to be higher than or equal to 0.1 Pa and lower than or equal

to 10 kPa, preferably higher than or equal to 1 Pa and lower than or equal to 1 kPa, further preferably higher than or equal to 5 Pa and lower than or equal to 100 Pa in the time range of 1 minute to 300 minutes, preferably 5 minutes to 120 minutes. After that, the transfer chamber **2704** and each of the chambers are evacuated in the time range of 5 minutes to 300 minutes, preferably 10 minutes to 120 minutes.

(394) Next, the chamber **2706b** and the chamber **2706c** are described with reference to a schematic cross-sectional view illustrated in FIG. **24**.

(395) The chamber **2706b** and the chamber **2706c** are chambers in which microwave treatment can be performed on an object, for example. Note that the chamber **2706b** is different from the chamber **2706c** only in the atmosphere in performing the microwave treatment. The other structures are common and thus collectively described below.

(396) The chamber **2706b** and the chamber **2706c** each include a slot antenna plate **2808**, a dielectric plate **2809**, a substrate holder **2812**, and an exhaust port **2819**. Furthermore, a gas supply source **2801**, a valve **2802**, a high-frequency generator **2803**, a waveguide **2804**, a mode converter **2805**, a gas pipe **2806**, a waveguide **2807**, a matching box **2815**, a high-frequency power source **2816**, a vacuum pump **2817**, and a valve **2818** are provided outside the chamber **2706b** and the chamber **2706c**, for example.

(397) The high-frequency generator **2803** is connected to the mode converter **2805** through the waveguide **2804**. The mode converter **2805** is connected to the slot antenna plate **2808** through the waveguide **2807**. The slot antenna plate **2808** is placed in contact with the dielectric plate **2809**. Furthermore, the gas supply source **2801** is connected to the mode converter **2805** through the valve **2802**. Then, gas is transferred to the chamber **2706b** and the chamber **2706c** through the gas pipe **2806** that runs through the mode converter **2805**, the waveguide **2807**, and the dielectric plate **2809**. Furthermore, the vacuum pump **2817** has a function of exhausting gas or the like from the chamber **2706b** and the chamber **2706c** through the valve **2818** and the exhaust port **2819**. Furthermore, the high-frequency power source **2816** is connected to the substrate holder **2812** through the matching box **2815**.

(398) The substrate holder **2812** has a function of holding a substrate **2811**. For example, the substrate holder **2812** has a function of an electrostatic chuck or a mechanical chuck for holding the substrate **2811**. Furthermore, the substrate holder **2812** has a function of an electrode to which electric power is supplied from the high-frequency power source **2816**. Furthermore, the substrate holder **2812** includes a heating mechanism **2813** therein and has a function of heating the substrate **2811**.

(399) As the vacuum pump **2817**, a dry pump, a mechanical booster pump, an ion pump, a titanium sublimation pump, a cryopump, or a turbomolecular pump can be used, for example. Furthermore, in addition to the vacuum pump **2817**, a cryotrap may be used. The use of the cryopump and the cryotrap is particularly preferable because water can be efficiently exhausted.

(400) Furthermore, for example, the heating mechanism **2813** is a heating mechanism that uses a resistance heater or the like for heating. Alternatively, a heating mechanism that uses heat conduction or heat radiation from a medium such as a heated gas for heating may be used. For example, RTA (Rapid Thermal Annealing) such as GRTA (Gas Rapid Thermal Annealing) or LRTA (Lamp Rapid Thermal Annealing) can be used. In GRTA, heat treatment is performed using a high-temperature gas. An inert gas is used as the gas.

(401) Furthermore, the gas supply source **2801** may be connected to a purifier through a mass flow controller. As the gas, a gas whose dew point is -80°C . or lower, preferably -100°C . or lower is preferably used. For example, an oxygen gas, a nitrogen gas, or a rare gas (an argon gas or the like) is used.

(402) As the dielectric plate **2809**, silicon oxide (quartz), aluminum oxide (alumina), or yttrium oxide (yttria) is used, for example. Furthermore, another protective layer may be further formed on a surface of the dielectric plate **2809**. For the protective layer, magnesium oxide, titanium oxide,

chromium oxide, tantalum oxide, hafnium oxide, silicon oxide, aluminum oxide, yttrium oxide, or the like is used. The dielectric plate **2809** is exposed to an especially high density region of high-density plasma **2810** described later; thus, provision of the protective layer can reduce the damage. Consequently, an increase in the number of particles or the like during the treatment can be inhibited.

(403) The high-frequency generator **2803** has a function of generating a microwave at, for example, higher than or equal to 0.3 GHz and lower than or equal to 3.0 GHz, higher than or equal to 0.7 GHz and lower than or equal to 1.1 GHz, or higher than or equal to 2.2 GHz and lower than or equal to 2.8 GHz. The microwave generated by the high-frequency generator **2803** is propagated to the mode converter **2805** through the waveguide **2804**. The mode converter **2805** converts the microwave propagated in the TE mode into a microwave in the TEM mode. Then, the microwave is propagated to the slot antenna plate **2808** through the waveguide **2807**. The slot antenna plate **2808** is provided with a plurality of slot holes, and the microwave passes through the slot holes and the dielectric plate **2809**. Then, an electric field is generated below the dielectric plate **2809**, and the high-density plasma **2810** can be generated. In the high-density plasma **2810**, ions and radicals based on the gas species supplied from the gas supply source **2801** are present. For example, oxygen radicals are present.

(404) At this time, the quality of a film or the like over the substrate **2811** can be modified by the ions and radicals generated in the high-density plasma **2810**. Note that it is preferable in some cases to apply a bias to the substrate **2811** side using the high-frequency power source **2816**. As the high-frequency power source **2816**, an RF (Radio Frequency) power source with a frequency of 13.56 MHz, 27.12 MHz, or the like is used, for example. The application of a bias to the substrate side allows ions in the high-density plasma **2810** to efficiently reach a deep portion of an opening portion of the film or the like over the substrate **2811**.

(405) For example, in the chamber **2706b** or the chamber **2706c**, oxygen radical treatment using the high-density plasma **2810** can be performed by introducing oxygen from the gas supply source **2801**.

(406) Next, the chamber **2706a** and the chamber **2706d** are described with reference to a schematic cross-sectional view illustrated in FIG. 25.

(407) The chamber **2706a** and the chamber **2706d** are chambers in which an object can be irradiated with an electromagnetic wave, for example. Note that the chamber **2706a** is different from the chamber **2706d** only in the kind of the electromagnetic wave. The other structures have many common portions and thus are collectively described below.

(408) The chamber **2706a** and the chamber **2706d** each include one or more lamps **2820**, a substrate holder **2825**, a gas inlet **2823**, and an exhaust port **2830**. Furthermore, a gas supply source **2821**, a valve **2822**, a vacuum pump **2828**, and a valve **2829** are provided outside the chamber **2706a** and the chamber **2706d**, for example.

(409) The gas supply source **2821** is connected to the gas inlet **2823** through the valve **2822**. The vacuum pump **2828** is connected to the exhaust port **2830** through the valve **2829**. The lamp **2820** is provided to face the substrate holder **2825**. The substrate holder **2825** has a function of holding a substrate **2824**. Furthermore, the substrate holder **2825** includes a heating mechanism **2826** therein and has a function of heating the substrate **2824**.

(410) As the lamp **2820**, a light source having a function of emitting an electromagnetic wave such as visible light or ultraviolet light is used, for example. For example, a light source having a function of emitting an electromagnetic wave which has a peak at a wavelength longer than or equal to 10 nm and shorter than or equal to 2500 nm, longer than or equal to 500 nm and shorter than or equal to 2000 nm, or longer than or equal to 40 nm and shorter than or equal to 340 nm is used.

(411) As the lamp **2820**, a light source such as a halogen lamp, a metal halide lamp, a xenon arc lamp, a carbon arc lamp, a high-pressure sodium lamp, or a high-pressure mercury lamp is used, for

example.

(412) For example, part or the whole of electromagnetic wave emitted from the lamp **2820** is absorbed by the substrate **2824**, so that the quality of a film or the like over the substrate **2824** can be modified. For example, generation or reduction of defects or removal of impurities can be performed. Note that generation or reduction of defects, removal of impurities, or the like can be efficiently performed while the substrate **2824** is heated.

(413) Alternatively, for example, the electromagnetic wave emitted from the lamp **2820** may generate heat in the substrate holder **2825** to heat the substrate **2824**. In this case, the substrate holder **2825** does not need to include the heating mechanism **2826** therein.

(414) For the vacuum pump **2828**, refer to the description of the vacuum pump **2817**. Furthermore, for the heating mechanism **2826**, refer to the description of the heating mechanism **2813**.

Furthermore, for the gas supply source **2821**, refer to the description of the gas supply source **2801**.

(415) A microwave treatment apparatus that can be used in this embodiment is not limited to the above. A microwave treatment apparatus **2900** illustrated in FIG. **26** can be used. The microwave treatment apparatus **2900** includes a quartz tube **2901**, the exhaust port **2819**, the gas supply source **2801**, the valve **2802**, the high-frequency generator **2803**, the waveguide **2804**, the gas pipe **2806**, the vacuum pump **2817**, and the valve **2818**. Furthermore, the microwave treatment apparatus **2900** includes a substrate holder **2902** that holds a plurality of substrates **2811** (**2811_1** to **2811_n**, n is an integer greater than or equal to 2) in the quartz tube **2901**. The microwave treatment apparatus **2900** may further include a heating means **2903** outside the quartz tube **2901**.

(416) The substrate placed in the quartz tube **2901** is irradiated with the microwave generated by the high-frequency generator **2803** and passing through the waveguide **2804**. The vacuum pump **2817** is connected to the exhaust port **2819** through the valve **2818** and can adjust the pressure inside the quartz tube **2901**. The gas supply source **2801** is connected to the gas pipe **2806** through the valve **2802** and can introduce a desired gas into the quartz tube **2901**. The heating means **2903** can heat the substrate **2811** in the quartz tube **2901** to a desired temperature. Alternatively, the heating means **2903** may heat the gas which is supplied from the gas supply source **2801**. With the use of the microwave treatment apparatus **2900**, the substrate **2811** can be subjected to heat treatment and microwave treatment at the same time. Alternatively, the substrate **2811** can be heated and then subjected to microwave treatment. Alternatively, the substrate **2811** can be subjected to microwave treatment and then heat treatment.

(417) All of the substrate **2811_1** to the substrate **2811_n** may be substrates to be treated where a semiconductor device or a memory device is to be formed, or some of the substrates may be dummy substrates. For example, the substrate **2811_1** and the substrate **2811_n** may be dummy substrates and the substrate **2811_2** to the substrate **2811_{n-1}** may be substrates to be treated. Alternatively, the substrate **2811_1**, the substrate **2811_2**, the substrate **2811_{n-1}**, and the substrate **2811_n** may be dummy substrates and the substrate **2811_3** to the substrate **2811_{n-2}** may be substrates to be treated. A dummy substrate is preferably used, in which case a plurality of substrates to be treated can be uniformly treated at the time of microwave treatment or heat treatment and a variation between the substrates to be treated can be reduced. For example, a dummy substrate is preferably placed over the substrate to be treated which is the closest to the high-frequency generator **2803** and the waveguide **2804**, in which case the substrate to be treated is inhibited from being directly exposed to a microwave.

(418) With the use of the above-described manufacturing apparatus, the quality of a film or the like can be modified while the entry of impurities into an object is inhibited.

(419) <Modification Example of Semiconductor Device>

(420) Examples of the semiconductor device of one embodiment of the present invention are described below with reference to FIG. **2A** to FIG. **2D**.

(421) FIG. **2A** is a top view of the semiconductor device. Moreover, FIG. **2B** is a cross-sectional view corresponding to a portion indicated by dashed-dotted line **A1-A2** in FIG. **2A**.

(422) Furthermore, FIG. 2C is a cross-sectional view corresponding to a portion indicated by dashed-dotted line A3-A4 in FIG. 2A. Furthermore, FIG. 2D is a cross-sectional view corresponding to a portion indicated by dashed-dotted line A5-A6 in FIG. 2A. Note that for clarity of the drawing, some components are omitted in the top view of FIG. 2A.

(423) Note that in the semiconductor device illustrated in FIG. 2A to FIG. 2D, components having the same functions as the components included in the semiconductor device described in <Structure example of semiconductor device> are denoted by the same reference numerals. Note that the materials described in detail in <Structure example of semiconductor device> can also be used as constituent materials of the semiconductor devices in this section.

(424) A semiconductor device illustrated in FIG. 2A to FIG. 2D is a modification example of the semiconductor device illustrated in FIG. 1A to FIG. 1D. The semiconductor device illustrated in FIG. 2A to FIG. 2D is different from the semiconductor device illustrated in FIG. 1A to FIG. 1D in that the insulator **283** is in contact with part of a top surface of the insulator **212**. Accordingly, the transistor **200** is placed in a region sealed with the insulator **283** and the insulator **212**. With the above structure, entry of hydrogen contained in a region outside the sealed region into the sealed region can be inhibited. Although FIG. 2A to FIG. 2D illustrate the transistor **200** having a structure in which the insulator **212** and the insulator **283** are each provided to have a single-layer structure, the present invention is not limited thereto. For example, the insulator **212** and the insulator **283** may each be provided to have a stacked-layer structure of two or more layers.

(425) <Application Example of Semiconductor Device>

(426) Examples of a semiconductor device including the transistor **200** of one embodiment of the present invention, which are different from the ones described in the above <Structure example of semiconductor device> and the above <Modification example of semiconductor device>, are described below with reference to FIG. 27A and FIG. 27B. Note that in the semiconductor devices illustrated in FIG. 27A and FIG. 27B, components having the same functions as the components included in the semiconductor device described in <Structure example of semiconductor device> (see FIG. 1A to FIG. 1D) are denoted by the same reference numerals. Note that the materials described in detail in <Structure example of semiconductor device> can be used as the constituent materials of the transistor **200** in this section.

(427) FIG. 27A and FIG. 27B each illustrate a structure in which transistors **200_1** to **200_n** are collectively sealed with the insulator **283** and the insulator **214**. Note that although the transistors **200_1** to **200_n** appear to be arranged in the channel length direction in FIG. 27A and FIG. 27B, the present invention is not limited thereto. The transistor **200_1** to the transistor **200_n** may be arranged in the channel width direction or may be arranged in a matrix. Alternatively, the transistors may be arranged without regularity depending on the design.

(428) As illustrated in FIG. 27A, a portion where the insulator **283** is in contact with the insulator **214** (hereinafter referred to as a sealing portion **265** in some cases) is formed outside the transistors **200_1** to **200_n**. The sealing portion **265** is formed to surround the transistors **200_1** to **200_n**. Such a structure enables the transistors **200_1** to **200_n** to be surrounded by the insulator **283** and the insulator **214**. Thus, some groups of a plurality of transistors (also referred to as transistor groups) surrounded by the sealing portion **265** are provided over a substrate.

(429) A dicing line (sometimes referred to as a scribe line, a dividing line, or a cutting line) may be provided to overlap the sealing portion **265**. The above substrate is divided at the dicing line, so that the transistor group surrounded by the sealing portion **265** is taken out as one chip.

(430) Although the transistors **200_1** to **200_n** are surrounded by one sealing portion **265** in the example illustrated in FIG. 27A, the present invention is not limited thereto. As illustrated in FIG. 27B, the transistors **200_1** to **200_n** may be surrounded by a plurality of sealing portions. In FIG. 27B, the transistors **200_1** to **200_n** are surrounded by a sealing portion **265a** and are further surrounded by an outer sealing portion **265b**.

(431) When the transistors **200_1** to **200_n** are surrounded by the plurality of sealing portions in

this manner, a portion where the insulator **283** is in contact with the insulator **214** increases, which further can improve adhesion between the insulator **283** and the insulator **214**. As a result, the transistors **200_1** to **200_n** can be more reliably sealed.

(432) In this case, a dicing line may be provided to overlap the sealing portion **265a** or the sealing portion **265b**, or may be provided between the sealing portion **265a** and the sealing portion **265b**.

(433) Although FIG. **27A** and FIG. **27B** illustrate the transistors as an example of a structure in which the insulator **283** and the insulator **214** are in contact with each other, the insulator **283** and the insulator **212** may be in contact with each other as shown in FIG. **2** and <Modification example of semiconductor device>.

(434) According to one embodiment of the present invention, a semiconductor device with a small variation in transistor characteristics can be provided. According to another embodiment of the present invention, a semiconductor device with favorable reliability can be provided. According to another embodiment of the present invention, a semiconductor device having favorable electrical characteristics can be provided. According to another embodiment of the present invention, a semiconductor device with a high on-state current can be provided. According to another embodiment of the present invention, a semiconductor device that can be miniaturized or highly integrated can be provided. According to another embodiment of the present invention, a semiconductor device with low power consumption can be provided.

(435) The structure, method, and the like described in this embodiment can be used in an appropriate combination with other structures, methods, and the like described in this embodiment, the other embodiments, or Examples.

Embodiment 2

(436) In this embodiment, one embodiment of a semiconductor device is described with reference to FIG. **28** to FIG. **33**.

(437) [Storage Device **1**]

(438) FIG. **28** illustrates an example of a semiconductor device (a storage device) of one embodiment of the present invention. The semiconductor device of one embodiment of the present invention has a structure in which the transistor **200** is provided above a transistor **300**, and a capacitor **100** is provided above the transistor **300** and the transistor **200**. The transistor **200** described in the above embodiment can be used as the transistor **200**.

(439) The transistor **200** is a transistor in which a channel is formed in a semiconductor layer including an oxide semiconductor. Since the transistor **200** has a low off-state current, a storage device that uses the transistor **200** can retain stored data for a long time. In other words, such a storage device does not require refresh operation or has extremely low frequency of the refresh operation, which leads to a sufficient reduction in power consumption of the storage device.

(440) In the semiconductor device illustrated in FIG. **28**, a wiring **1001** is electrically connected to a source of the transistor **300**, and a wiring **1002** is electrically connected to a drain of the transistor **300**. In addition, a wiring **1003** is electrically connected to one of the source and the drain of the transistor **200**, a wiring **1004** is electrically connected to the first gate of the transistor **200**, and a wiring **1006** is electrically connected to the second gate of the transistor **200**. A gate of the transistor **300** and the other of the source and the drain of the transistor **200** are electrically connected to one electrode of the capacitor **100**, and a wiring **1005** is electrically connected to the other electrode of the capacitor **100**.

(441) The storage device illustrated in FIG. **28** can form a memory cell array when arranged in a matrix.

(442) <Transistor **300**>

(443) The transistor **300** is provided on a substrate **311** and includes a conductor **316** functioning as a gate, an insulator **315** functioning as a gate insulator, a semiconductor region **313** formed of part of the substrate **311**, and a low-resistance region **314a** and a low-resistance region **314b** functioning as a source region and a drain region. The transistor **300** may be a p-channel transistor or an n-

channel transistor.

(444) Here, in the transistor **300** illustrated in FIG. **28**, the semiconductor region **313** (part of the substrate **311**) where a channel is formed has a protruding shape. In addition, the conductor **316** is provided to cover a side surface and a top surface of the semiconductor region **313** with the insulator **315** therebetween. Note that a material adjusting the work function may be used for the conductor **316**. Such a transistor **300** is also referred to as a FIN-type transistor because it utilizes a protruding portion of a semiconductor substrate. Note that an insulator functioning as a mask for forming the protruding portion may be included in contact with an upper portion of the protruding portion. Furthermore, although the case where the protruding portion is formed by processing part of the semiconductor substrate is described here, a semiconductor film having a protruding shape may be formed by processing an SOI substrate.

(445) Note that the transistor **300** illustrated in FIG. **28** is an example and the structure is not limited thereto; an appropriate transistor is used in accordance with a circuit structure or a driving method.

(446) <Capacitor **100**>

(447) The capacitor **100** is provided above the transistor **200**. The capacitor **100** includes a conductor **110** functioning as a first electrode, a conductor **120** functioning as a second electrode, and an insulator **130** functioning as a dielectric. Here, for the insulator **130**, the insulator that can be used as the insulator **286** described in the above embodiment is preferably used.

(448) For example, a conductor **112** and the conductor **110** can be formed at the same time. Note that the conductor **112** has a function of a plug or a wiring that is electrically connected to the capacitor **100**, the transistor **200**, or the transistor **300**.

(449) Although the conductor **112** and the conductor **110** having a single-layer structure are illustrated in FIG. **28**, the structure is not limited thereto; a stacked-layer structure of two or more layers may be employed. For example, between a conductor having a barrier property and a conductor having high conductivity, a conductor that is highly adhesive to the conductor having a barrier property and the conductor having high conductivity may be formed.

(450) The insulator **130** can be provided as stacked layers or a single layer using, for example, silicon oxide, silicon oxynitride, silicon nitride oxide, silicon nitride, aluminum oxide, aluminum oxynitride, aluminum nitride oxide, aluminum nitride, hafnium oxide, hafnium oxynitride, hafnium nitride oxide, or hafnium nitride.

(451) For example, for the insulator **130**, a stacked-layer structure of a material with high dielectric strength such as silicon oxynitride and a high permittivity (high-k) material is preferably used. In the capacitor **100** having such a structure, a sufficient capacitance can be ensured owing to the high permittivity (high-k) insulator, and the dielectric strength can be increased owing to the insulator with high dielectric strength, so that the electrostatic breakdown of the capacitor **100** can be inhibited.

(452) Examples of the high permittivity (high-k) material (a material having a high dielectric constant) include gallium oxide, hafnium oxide, zirconium oxide, an oxide containing aluminum and hafnium, an oxynitride containing aluminum and hafnium, an oxide containing silicon and hafnium, an oxynitride containing silicon and hafnium, and a nitride containing silicon and hafnium.

(453) Examples of a material with high dielectric strength (a material having a low dielectric constant) include silicon oxide, silicon oxynitride, silicon nitride oxide, silicon nitride, silicon oxide to which fluorine is added, silicon oxide to which carbon is added, silicon oxide to which carbon and nitrogen are added, porous silicon oxide, and a resin.

(454) <Wiring Layer>

(455) Wiring layers provided with an interlayer film, a wiring, a plug, and the like may be provided between the components. A plurality of wiring layers can be provided in accordance with design. Here, a plurality of conductors functioning as plugs or wirings are collectively denoted by the same

reference numeral in some cases. Furthermore, in this specification and the like, a wiring and a plug electrically connected to the wiring may be a single component. That is, there are cases where part of a conductor functions as a wiring and part of a conductor functions as a plug.

(456) For example, an insulator **320**, an insulator **322**, an insulator **324**, and an insulator **326** are sequentially stacked over the transistor **300** as interlayer films. A conductor **328**, a conductor **330**, and the like that are electrically connected to the capacitor **100** or the transistor **200** are embedded in the insulator **320**, the insulator **322**, the insulator **324**, and the insulator **326**. Note that the conductor **328** and the conductor **330** function as a plug or a wiring.

(457) The insulators functioning as interlayer films may also function as planarization films that cover uneven shapes therebelow. For example, a top surface of the insulator **322** may be planarized by planarization treatment using a chemical mechanical polishing (CMP) method or the like to improve planarity.

(458) A wiring layer may be provided over the insulator **326** and the conductor **330**. For example, in FIG. **28**, an insulator **350**, an insulator **352**, and an insulator **354** are stacked sequentially. Furthermore, a conductor **356** is formed in the insulator **350**, the insulator **352**, and the insulator **354**. The conductor **356** functions as a plug or a wiring.

(459) Similarly, a conductor **218**, a conductor (the conductor **205**) included in the transistor **200**, and the like are embedded in an insulator **210**, the insulator **212**, the insulator **214**, and the insulator **216**. Note that the conductor **218** has a function of a plug or a wiring that is electrically connected to the capacitor **100** or the transistor **300**. In addition, an insulator **150** is provided over the conductor **120** and the insulator **130**.

(460) Here, like the insulator **241** described in the above embodiment, an insulator **217** is provided in contact with a side surface of the conductor **218** functioning as a plug. The insulator **217** is provided in contact with an inner wall of an opening formed in the insulator **210**, the insulator **212**, the insulator **214**, and the insulator **216**. That is, the insulator **217** is provided between the conductor **218** and each of the insulator **210**, the insulator **212**, the insulator **214**, and the insulator **216**. Note that the conductor **205** and the conductor **218** can be formed in parallel; thus, the insulator **217** is sometimes formed in contact with the side surface of the conductor **205**.

(461) As the insulator **217**, an insulator such as silicon nitride, aluminum oxide, or silicon nitride oxide may be used, for example. Since the insulator **217** is provided in contact with the insulator **210**, the insulator **212**, the insulator **214**, and the insulator **222**, entry of impurities such as water and hydrogen into the oxide **230** through the conductor **218** from the insulator **210**, the insulator **216**, or the like can be inhibited. In particular, silicon nitride is suitable because of its high blocking property against hydrogen. Moreover, oxygen contained in the insulator **210** or the insulator **216** can be prevented from being absorbed by the conductor **218**.

(462) The insulator **217** can be formed in a manner similar to that of the insulator **241**. For example, silicon nitride is deposited by a PEALD method and an opening reaching the conductor **356** is formed by anisotropic etching.

(463) Examples of an insulator that can be used as an interlayer film include an insulating oxide, an insulating nitride, an insulating oxynitride, an insulating nitride oxide, an insulating metal oxide, an insulating metal oxynitride, and an insulating metal nitride oxide.

(464) For example, when a material having a low dielectric constant is used for the insulator functioning as an interlayer film, parasitic capacitance generated between wirings can be reduced. Thus, a material is preferably selected depending on the function of an insulator.

(465) For example, as the insulator **150**, the insulator **210**, the insulator **352**, the insulator **354**, and the like, an insulator having a low dielectric constant is preferably included. For example, the insulator preferably includes silicon oxide to which fluorine is added, silicon oxide to which carbon is added, silicon oxide to which carbon and nitrogen are added, porous silicon oxide, a resin, or the like. Alternatively, the insulator preferably has a stacked-layer structure of a resin and silicon oxide, silicon oxynitride, silicon nitride oxide, silicon nitride, silicon oxide to which fluorine is added,

silicon oxide to which carbon is added, silicon oxide to which carbon and nitrogen are added, or porous silicon oxide. When silicon oxide or silicon oxynitride, which is thermally stable, is combined with a resin, the stacked-layer structure can have thermal stability and a low dielectric constant. Examples of the resin include polyester, polyolefin, polyamide (e.g., nylon and aramid), polyimide, polycarbonate, and acrylic.

(466) When a transistor using an oxide semiconductor is surrounded by an insulator having a function of inhibiting passage of oxygen and impurities such as hydrogen, the electrical characteristics of the transistor can be stable. Thus, the insulator having a function of inhibiting passage of oxygen and impurities such as hydrogen can be used for the insulator **214**, the insulator **212**, the insulator **350**, and the like.

(467) As the insulator having a function of inhibiting passage of oxygen and impurities such as hydrogen, a single layer or stacked layers of an insulator containing, for example, boron, carbon, nitrogen, oxygen, fluorine, magnesium, aluminum, silicon, phosphorus, chlorine, argon, gallium, germanium, yttrium, zirconium, lanthanum, neodymium, hafnium, or tantalum are used.

(468) Specifically, as the insulator having a function of inhibiting passage of oxygen and impurities such as hydrogen, a metal oxide such as aluminum oxide, magnesium oxide, gallium oxide, germanium oxide, yttrium oxide, zirconium oxide, lanthanum oxide, neodymium oxide, hafnium oxide, or tantalum oxide; silicon nitride oxide; silicon nitride; or the like can be used.

(469) As the conductor that can be used for a wiring or a plug, a material containing one or more kinds of metal elements selected from aluminum, chromium, copper, silver, gold, platinum, tantalum, nickel, titanium, molybdenum, tungsten, hafnium, vanadium, niobium, manganese, magnesium, zirconium, beryllium, indium, ruthenium, and the like can be used. Alternatively, a semiconductor having high electrical conductivity, typified by polycrystalline silicon containing an impurity element such as phosphorus, or silicide such as nickel silicide may be used.

(470) For example, for the conductor **328**, the conductor **330**, the conductor **356**, the conductor **218**, the conductor **112**, and the like, a single layer or stacked layers of conductive material such as a metal material, an alloy material, a metal nitride material, or a metal oxide material that is formed using the above materials can be used. It is preferable to use a high-melting-point material that has both heat resistance and conductivity, such as tungsten or molybdenum, and it is preferable to use tungsten. Alternatively, it is preferable to use a low-resistance conductive material such as aluminum or copper. The use of a low-resistance conductive material can reduce wiring resistance.

(471) <Wiring or Plug in Layer Provided with Oxide Semiconductor>

(472) In the case where an oxide semiconductor is used in the transistor **200**, an insulator including an excess-oxygen region is provided in the vicinity of the oxide semiconductor in some cases. In that case, an insulator having a barrier property is preferably provided between the insulator including the excess-oxygen region and a conductor provided in the insulator including the excess-oxygen region.

(473) For example, in FIG. **28**, the insulator **241** is preferably provided between the conductor **240** and the insulator **280** including excess oxygen. Since the insulator **241** is provided in contact with the insulator **222**, the insulator **282**, and the insulator **283**, the transistor **200** can be sealed with the insulators having a barrier property.

(474) That is, the insulator **241** can inhibit excess oxygen contained in the insulator **280** from being absorbed by the conductor **240**. In addition, providing the insulator **241** can inhibit diffusion of hydrogen, which is an impurity, into the transistor **200** through the conductor **240**.

(475) The insulator **241** is preferably formed using an insulating material having a function of inhibiting diffusion of oxygen and impurities such as water and hydrogen. For example, silicon nitride, silicon nitride oxide, aluminum oxide, hafnium oxide, or the like is preferably used. In particular, silicon nitride is preferable because of its high blocking property against hydrogen. Other than that, a metal oxide such as magnesium oxide, gallium oxide, germanium oxide, yttrium oxide, zirconium oxide, lanthanum oxide, neodymium oxide, or tantalum oxide can be used, for

example.

(476) As described in the above embodiment, the transistor **200** may be sealed with the insulator **212**, the insulator **214**, the insulator **282**, and the insulator **283**. Such a structure can inhibit entry of hydrogen contained in the insulator **274**, the insulator **150**, or the like into the insulator **280** or the like.

(477) Here, the conductor **240** penetrates the insulator **283** and the insulator **282**, and the conductor **218** penetrates the insulator **214** and the insulator **212**; however, as described above, the insulator **241** is provided in contact with the conductor **240**, and the insulator **217** is provided in contact with the conductor **218**. This can reduce the amount of hydrogen entering the inside of the insulator **212**, the insulator **214**, the insulator **282**, and the insulator **283** through the conductor **240** and the conductor **218**. In this manner, the transistor **200** is sealed with the insulator **212**, the insulator **214**, the insulator **282**, the insulator **283**, the insulator **241**, and the insulator **217**, so that impurities such as hydrogen contained in the insulator **274** or the like can be inhibited from entering from the outside.

(478) <Dicing Line>

(479) A dicing line (sometimes referred to as a scribe line, a dividing line, or a cutting line) which is provided when a large-sized substrate is divided into semiconductor elements so that a plurality of semiconductor devices are each formed in a chip form is described below. Examples of a dividing method include the case where a groove (a dicing line) for dividing the semiconductor elements is formed on the substrate, and then the substrate is cut along the dicing line to divide (split) it into a plurality of semiconductor devices.

(480) Here, for example, as illustrated in FIG. **28**, a region in which the insulator **283** and the insulator **214** are in contact with each other is preferably designed to overlap the dicing line. That is, an opening is provided in the insulator **282**, the insulator **280**, the insulator **272**, the insulator **222**, and the insulator **216** in the vicinity of a region to be the dicing line that is provided on an outer edge of the memory cell including the plurality of transistors **200**.

(481) That is, in the opening provided in the insulator **282**, the insulator **280**, the insulator **272**, the insulator **222**, and the insulator **216**, the insulator **214** is in contact with the insulator **283**.

(482) For example, an opening may be provided in the insulator **282**, the insulator **280**, the insulator **272**, the insulator **222**, the insulator **216**, and the insulator **214**. With such a structure, in the opening provided in the insulator **282**, the insulator **280**, the insulator **272**, the insulator **222**, the insulator **216**, and the insulator **214**, the insulator **212** is in contact with the insulator **283**. Here, the insulator **212** and the insulator **283** may be formed using the same material and the same method. When the insulator **212** and the insulator **283** are formed using the same material and the same method, the adhesion therebetween can be increased. For example, silicon nitride is preferably used.

(483) With the structure, the transistors **200** can be surrounded by the insulator **212**, the insulator **214**, the insulator **282**, and the insulator **283**. Since at least one of the insulator **212**, the insulator **214**, the insulator **282**, and the insulator **283** has a function of inhibiting diffusion of oxygen, hydrogen, and water, even when the substrate is divided into circuit regions each of which is provided with the semiconductor elements described in this embodiment to be processed into a plurality of chips, entry and diffusion of impurities such as hydrogen and water from the direction of the side surface of the divided substrate into the transistor **200** can be prevented.

(484) With the structure, excess oxygen in the insulator **280** and the insulator **224** can be prevented from diffusing to the outside. Accordingly, excess oxygen in the insulator **280** and the insulator **224** is efficiently supplied to the oxide where the channel is formed in the transistor **200**. The oxygen can reduce oxygen vacancies in the oxide where the channel is formed in the transistor **200**. Thus, the oxide where the channel is formed in the transistor **200** can be an oxide semiconductor with a low density of defect states and stable characteristics. That is, the transistor **200** can have a small variation in the electrical characteristics and higher reliability.

(485) Note that although the capacitor **100** of the storage device illustrated in FIG. **28** has a planar shape, the storage device described in this embodiment is not limited thereto. For example, the capacitor **100** may have a cylindrical shape as illustrated in FIG. **29**. Note that the structure below and including the insulator **150** of a storage device illustrated in FIG. **29** is similar to that of the semiconductor device illustrated in FIG. **28**.

(486) The capacitor **100** illustrated in FIG. **29** includes the insulator **150** over the insulator **130**, an insulator **142** over the insulator **150**, a conductor **115** placed in an opening formed in the insulator **150** and the insulator **142**, an insulator **145** over the conductor **115** and the insulator **142**, a conductor **125** over the insulator **145**, and an insulator **152** over the conductor **125** and the insulator **145**. Here, at least parts of the conductor **115**, the insulator **145**, and the conductor **125** are placed in the opening formed in the insulator **150** and the insulator **142**.

(487) The conductor **115** functions as a lower electrode of the capacitor **100**, the conductor **125** functions as an upper electrode of the capacitor **100**, and the insulator **145** functions as a dielectric of the capacitor **100**. The capacitor **100** has a structure in which the upper electrode and the lower electrode face each other with the dielectric sandwiched therebetween on a side surface as well as a bottom surface of the opening in the insulator **150** and the insulator **142**; thus, the capacitance per unit area can be increased. Thus, the deeper the opening is, the larger the capacitance of the capacitor **100** can be. Increasing the capacitance per unit area of the capacitor **100** in this manner can promote miniaturization or higher integration of the semiconductor device.

(488) An insulator that can be used as the insulator **280** can be used as the insulator **152**. The insulator **142** preferably functions as an etching stopper at the time of forming the opening in the insulator **150** and is formed using an insulator that can be used as the insulator **214**.

(489) The shape of the opening formed in the insulator **150** and the insulator **142** when seen from above may be a quadrangular shape, a polygonal shape other than a quadrangular shape, a polygonal shape with rounded corners, or a circular shape including an elliptical shape. Here, the area where the opening and the transistor **200** overlap each other is preferably large in the top view. Such a structure can reduce the area occupied by the semiconductor device including the capacitor **100** and the transistor **200**.

(490) The conductor **115** is placed in contact with the opening formed in the insulator **142** and the insulator **150**. A top surface of the conductor **115** is preferably substantially level with a top surface of the insulator **142**. Furthermore, a bottom surface of the conductor **115** is in contact with the conductor **110** through an opening in the insulator **130**. The conductor **115** is preferably deposited by an ALD method, a CVD method, or the like; for example, a conductor that can be used for the conductor **205** is used.

(491) The insulator **145** is placed to cover the conductor **115** and the insulator **142**. The insulator **145** is preferably deposited by an ALD method or a CVD method, for example. The insulator **145** can be provided to have stacked layers or a single layer using, for example, silicon oxide, silicon oxynitride, silicon nitride oxide, silicon nitride, zirconium oxide, aluminum oxide, aluminum oxynitride, aluminum nitride oxide, aluminum nitride, hafnium oxide, hafnium oxynitride, hafnium nitride oxide, or hafnium nitride. As the insulator **145**, an insulating film in which zirconium oxide, aluminum oxide, and zirconium oxide are stacked in this order can be used, for example.

(492) For the insulator **145**, a material with high dielectric strength, such as silicon oxynitride, or a high permittivity (high-k) material is preferably used. Alternatively, a stacked-layer structure of a material with high dielectric strength and a high permittivity (high-k) material may be used.

(493) Examples of the high permittivity (high-k) material (a material having a high dielectric constant) include gallium oxide, hafnium oxide, zirconium oxide, an oxide containing aluminum and hafnium, an oxynitride containing aluminum and hafnium, an oxide containing silicon and hafnium, an oxynitride containing silicon and hafnium, and a nitride containing silicon and hafnium. The use of such a high-k material can ensure sufficient capacitance of the capacitor **100** even when the insulator **145** has a large thickness. When the insulator **145** has a large thickness,

generation of a leakage current between the conductor **115** and the conductor **125** can be inhibited. (494) Examples of the material with high dielectric strength include silicon oxide, silicon oxynitride, silicon nitride oxide, silicon nitride, silicon oxide to which fluorine is added, silicon oxide to which carbon is added, silicon oxide to which carbon and nitrogen are added, porous silicon oxide, and a resin. For example, it is possible to use an insulating film in which silicon nitride (SiN.sub.x) deposited by a PEALD method, silicon oxide (SiO.sub.x) deposited by a PEALD method, and silicon nitride (SiN.sub.x) deposited by a PEALD method are stacked in this order. Alternatively, an insulating film in which zirconium oxide, silicon oxide deposited by an ALD method, and zirconium oxide are stacked in this order can be used. The use of such an insulator with high dielectric strength can increase the dielectric strength and inhibit electrostatic breakdown of the capacitor **100**.

(495) The conductor **125** is placed to fill the opening formed in the insulator **142** and the insulator **150**. The conductor **125** is electrically connected to the wiring **1005** through a conductor **140** and a conductor **153**. The conductor **125** is preferably deposited by an ALD method, a CVD method, or the like and is formed using a conductor that can be used as the conductor **205**, for example.

(496) The conductor **153** is provided over an insulator **154** and is covered with an insulator **156**. The conductor **153** is formed using a conductor that can be used as the conductor **112**, and the insulator **156** is formed using an insulator that can be used as the insulator **152**. Here, the conductor **153** is in contact with a top surface of the conductor **140** and functions as a terminal of the capacitor **100**, the transistor **200**, or the transistor **300**.

(497) [Storage Device 2]

(498) FIG. **30A** and FIG. **30B** illustrate examples of a semiconductor device (a storage device) of one embodiment of the present invention.

(499) <Structure Example 1 of Memory Device>

(500) FIG. **30A** is a cross-sectional view of a semiconductor device including a memory device **290**. The memory device **290** illustrated in FIG. **30A** includes a capacitor device **292** besides the transistor **200** illustrated in FIG. **1A** to FIG. **1D**. FIG. **30A** corresponds to a cross-sectional view of the transistor **200** in the channel length direction.

(501) The capacitor device **292** includes the conductor **242b**; the insulator **271b** provided over the conductor **242b**; the insulator **272** provided in contact with a top surface of the insulator **271b**, a side surface of the insulator **271b**, and a side surface of the conductor **242b**; and a conductor **294** over the insulator **272**. In other words, the capacitor device **292** forms a MIM (Metal-Insulator-Metal) capacitor. Note that one of a pair of electrodes included in the capacitor device **292**, i.e., the conductor **242b**, can also serve as the source electrode of the transistor. The dielectric layer included in the capacitor device **292** can also serve as a protective layer provided in the transistor, i.e., the insulator **271** and the insulator **272**. Thus, the manufacturing process of the capacitor device **292** can also serve as part of the manufacturing process of the transistor, improving the productivity of the semiconductor device. Furthermore, one of a pair of electrodes included in the capacitor device **292**, that is, the conductor **242b**, also serves as the source electrode of the transistor; therefore, the area in which the transistor and the capacitor device are placed can be reduced.

(502) Note that the conductor **294** can be formed using, for example, a material that can be used for the conductor **242**.

(503) <Structure Example 2 of Memory Device>

(504) FIG. **30B** is a cross-sectional view of a semiconductor device including the memory device **290**, which has a structure different from that illustrated in FIG. **30A**. The memory device **290** illustrated in FIG. **30B** includes the capacitor device **292** besides the transistor **200** illustrated in FIG. **1A** to FIG. **1D**. Here, part of the capacitor device **292** illustrated in FIG. **30B** is provided in an opening formed in the insulator **280**, the insulator **272**, and the insulator **271b**, which is different from the capacitor device **292** illustrated in FIG. **30A**. FIG. **30B** corresponds to a cross-sectional

view of the transistor **200** in the channel length direction.

(505) The capacitor device **292** includes the conductor **242b**, an insulator **293** provided over the conductor **242b**, and the conductor **294** provided over the insulator **293**. Here, the insulator **293** and the conductor **294** are placed in the opening formed in the insulator **280**, the insulator **272**, and the insulator **271b**. The insulator **293** is provided in contact with a bottom surface and a sidewall of the opening. That is, the insulator **293** is in contact with the top surface of the conductor **242b**, a side surface of the insulator **271b**, a side surface of the insulator **272**, and a side surface of the insulator **280**. The insulator **293** is provided to form a depressed portion along the shape of the opening. The conductor **294** is placed in contact with a top surface and a side surface of the insulator **293** so as to fill the depressed portion. Note that the top-surface levels of the insulator **293** and the conductor **294** are substantially the same as the top-surface levels of the insulator **280**, the insulator **250**, and the conductor **260** in some cases.

(506) Here, the conductor **242b** functions as a lower electrode of the capacitor device **292**, the conductor **294** functions as an upper electrode of the capacitor device **292**, and the insulator **293** functions as a dielectric of the capacitor device **292**. Thus, the capacitor device **292** forms an MIM capacitor. Note that one of a pair of electrodes included in the capacitor device **292**, i.e., the conductor **242b**, can also serve as the source electrode of the transistor. Thus, the manufacturing process of the capacitor device **292** can also serve as part of the manufacturing process of the transistor, improving the productivity of the semiconductor device. Since the insulator **293** can be provided independently of the structure of the transistor **200**, a structure and a material of the insulator **293** can be selected as appropriate in accordance with performance required for the capacitor device **292**. Furthermore, one of a pair of electrodes included in the capacitor device **292**, i.e., the conductor **242b**, also serves as the source electrode of the transistor; therefore, the area in which the transistor and the capacitor device are placed can be reduced.

(507) A high permittivity (high-k) material is preferably used for the insulator **293**. Examples of the high permittivity (high-k) material (a material having a high dielectric constant) include gallium oxide, hafnium oxide, zirconium oxide, aluminum oxide, aluminum oxynitride, aluminum nitride oxide, aluminum nitride, hafnium oxide, hafnium oxynitride, hafnium nitride oxide, hafnium nitride, an oxide containing aluminum and hafnium, an oxynitride containing aluminum and hafnium, an oxide containing silicon and hafnium, an oxynitride containing silicon and hafnium, and a nitride containing silicon and hafnium. Stack of these high permittivity materials may be used as the insulator **293**. As the insulator **293**, an insulating film in which zirconium oxide, aluminum oxide, and zirconium oxide are stacked in this order can be used, for example.

(508) The conductor **294** can be formed using, for example, a material that can be used for the conductor **260**. The conductor **294** may have a stacked-layer structure like the conductor **260**.

(509) The insulator **293** and the conductor **294** may be formed before the deposition of the insulator **282**, that is, before the step illustrated in FIG. **19**. The insulator **293** and the conductor **294** can be formed by a method similar to that for forming the insulator **250** and the conductor **260**. That is, the insulator **293** and the conductor **294** may be formed in such a manner that an opening is formed in the insulator **280**, the insulator **272**, and the insulator **271b**, a stacked film to be the insulator **293** and the conductor **294** is deposited to be embedded in the opening, and the stacked film is partly removed by CMP treatment.

(510) <Modification Example of Memory Device>

(511) Examples of a semiconductor device of one embodiment of the present invention including the transistor **200** and the capacitor device **292**, which are different from the one described above in <Structure example 1 of memory device>, are described below with reference to FIG. **31A**, FIG. **31B**, FIG. **32**, and FIG. **33**. Note that in the semiconductor devices illustrated in FIG. **31A**, FIG. **31B**, FIG. **32**, and FIG. **33**, structures having the same function as those included in the semiconductor devices described in the above embodiment and <Structure example 1 of memory device> (see FIG. **30A**) are denoted by the same reference numerals. Note that the materials

described in detail in the above embodiment and <Structure example 1 of memory device> can be used as constituent materials of the transistor **200** and the capacitor device **292** in this section. The memory devices in FIG. **31A**, FIG. **31B**, FIG. **32**, FIG. **33**, and the like are the memory device illustrated in FIG. **30A**, but not limited to this. For example, the memory device illustrated in FIG. **30B** or the like may be used.

(512) <<Modification Example 1 of Memory Device>>

(513) An example of a semiconductor device **600** of one embodiment of the present invention including a transistor **200a**, a transistor **200b**, a capacitor device **292a**, and a capacitor device **292b** is described below with reference to FIG. **31A**.

(514) FIG. **31A** is a cross-sectional view of the semiconductor device **600** including the transistor **200a**, the transistor **200b**, the capacitor device **292a**, and the capacitor device **292b** in the channel length direction. Here, the capacitor device **292a** includes the conductor **242a**; the insulator **271a** over the conductor **242a**; the insulator **272** in contact with a top surface of the insulator **271a**, a side surface of the insulator **271a**, and a side surface of the conductor **242a**; and a conductor **294a** over the insulator **272**. The capacitor device **292b** includes the conductor **242b**; the insulator **271b** over the conductor **242b**; the insulator **272** in contact with the top surface of the insulator **271b**, the side surface of the insulator **271b**, and the side surface of the conductor **242b**; and a conductor **294b** over the insulator **272**.

(515) The semiconductor device **600** has a line-symmetric structure with respect to dashed-dotted line A3-A4 as illustrated in FIG. **31A**. A conductor **242c** serves as one of a source electrode and a drain electrode of the transistor **200a** and one of a source electrode and a drain electrode of the transistor **200b**. An insulator **271c** is provided over the conductor **242c**. The conductor **240** functioning as a plug connects the conductor **246** functioning as a wiring to the transistor **200a** and the transistor **200b**. With the above connection structure between the two transistors, the two capacitor devices, the wiring, and the plug, a semiconductor device that can be miniaturized or highly integrated can be provided.

(516) The structure examples of the semiconductor device illustrated in FIG. **30A** can be referred to for the structures and the effects of the transistor **200a**, the transistor **200b**, the capacitor device **292a**, and the capacitor device **292b**.

(517) <<Modification Example 2 of Memory Device>>

(518) In the above description, the semiconductor device including the transistor **200a**, the transistor **200b**, the capacitor device **292a**, and the capacitor device **292b** is given as a structure example; however, the semiconductor device described in this embodiment is not limited thereto. For example, as illustrated in FIG. **31B**, a structure may be employed in which the semiconductor device **600** and a semiconductor device having a structure similar to that of the semiconductor device **600** are connected through a capacitor portion. In this specification, the semiconductor device including the transistor **200a**, the transistor **200b**, the capacitor device **292a**, and the capacitor device **292b** is referred to as a cell. For the structures of the transistor **200a**, the transistor **200b**, the capacitor device **292a**, and the capacitor device **292b**, the above description of the transistor **200a**, the transistor **200b**, the capacitor device **292a**, and the capacitor device **292b** can be referred to.

(519) FIG. **31B** is a cross-sectional view in which the semiconductor device **600** including the transistor **200a**, the transistor **200b**, the capacitor device **292a**, and the capacitor device **292b**, and a cell having a structure similar to that of the semiconductor device **600** are connected through a capacitor portion.

(520) As illustrated in FIG. **31B**, the conductor **294b** functioning as one electrode of the capacitor device **292b** included in the semiconductor device **600** also serves as one electrode of a capacitor device included in a semiconductor device **601** having a structure similar to that of the semiconductor device **600**. Although not illustrated, the conductor **294a** functioning as one electrode of the capacitor device **292a** included in the semiconductor device **600** also serves as one

electrode of a capacitor device included in a semiconductor device on the left side of the semiconductor device **600**, that is, a semiconductor device adjacent to the semiconductor device **600** in the A1 direction in FIG. **31B**. The cell on the right side of the semiconductor device **601**, that is, the cell in the A2 direction in FIG. **31B**, has a similar structure. That is, a cell array (also referred to as a memory device layer) can be formed. With such a structure of the cell array, space between adjacent cells can be reduced; thus, the projected area of the cell array can be reduced and high integration can be achieved. When the cells illustrated in FIG. **31B** are arranged in a matrix, a matrix-shape cell array can be formed.

(521) When the transistor **200a**, the transistor **200b**, the capacitor device **292a**, and the capacitor device **292b** are formed to have the structures described in this embodiment as described above, the area of the cell can be reduced and the semiconductor device including a cell array can be miniaturized or highly integrated.

(522) Furthermore, the cell array may have a stacked-layer structure instead of a single-layer structure. FIG. **32** illustrates a cross-sectional view of n layers of cell arrays **610** that are stacked. When a plurality of cell arrays (a cell array **610_1** to a cell array **610_n**) are stacked as illustrated in FIG. **32**, cells can be integrally placed without increasing the area occupied by the cell arrays. In other words, a 3D cell array can be formed.

(523) <Modification Example 3 of Memory Device>

(524) FIG. **33** illustrates an example in which a memory unit **470** includes a transistor layer **413** including a transistor **200T** and four memory device layers **415** (a memory device layer **415_1** to a memory device layer **415_4**).

(525) The memory device layer **415_1** to the memory device layer **415_4** each include a plurality of memory devices **420**.

(526) The memory device **420** is electrically connected to the memory device **420** included in a different memory device layer **415** and the transistor **200T** included in the transistor layer **413** through a conductor **424** and the conductor **205**.

(527) The memory unit **470** is sealed with the insulator **212**, the insulator **214**, the insulator **282**, and the insulator **283** (such a structure is referred to as a sealing structure below for convenience). The insulator **274** is provided in the periphery of the insulator **283**. A conductor **440** is provided in the insulator **274**, the insulator **283**, and the insulator **212**, and is electrically connected to an element layer **411**.

(528) The insulator **280** is provided in the sealing structure. The insulator **280** has a function of releasing oxygen by heating. Alternatively, the insulator **280** includes an excess-oxygen region.

(529) The insulator **212** and the insulator **283** are each suitably formed using a material having a high blocking property against hydrogen. The insulator **214** and the insulator **282** are each suitably formed using a material having a function of capturing hydrogen or fixing hydrogen.

(530) Examples of the material having a high blocking property against hydrogen include silicon nitride and silicon nitride oxide. Examples of the material having a function of capturing or fixing hydrogen include aluminum oxide, hafnium oxide, and an oxide containing aluminum and hafnium (hafnium aluminate).

(531) For the crystal structure of materials used for the insulator **212**, the insulator **214**, the insulator **282**, and the insulator **283**, an amorphous or crystalline structure may be employed, although there is no particular limitation. For example, it is suitable to use an amorphous aluminum oxide film as the material having a function of capturing or fixing hydrogen. Amorphous aluminum oxide sometimes captures or fixes hydrogen more than aluminum oxide with high crystallinity.

(532) Here, the following model can be given as the model of excess oxygen in the insulator **280** with respect to the diffusion of hydrogen from an oxide semiconductor in contact with the insulator **280**.

(533) Hydrogen in the oxide semiconductor diffuses into other structure bodies through the insulator **280** in contact with the oxide semiconductor. Owing to the hydrogen diffusion, the excess

oxygen in the insulator **280** reacts with hydrogen in the oxide semiconductor, which yields the OH bonding to diffuse in the insulator **280**. The hydrogen atom having the OH bonding reacts with the oxygen atom bonded to an atom (such as a metal atom) in the insulator **282** in reaching a material that has a function of capturing or fixing hydrogen (typically the insulator **282**), and is captured or fixed in the insulator **282**. The oxygen atom which had the OH bonding of the excess oxygen may remain as excess oxygen in the insulator **280**. That is, it is highly probable that the excess oxygen in the insulator **280** serves as a bridge in the diffusion of the hydrogen.

(534) A manufacturing process of the semiconductor device is one of important factors for the model.

(535) For example, the insulator **280** containing excess oxygen is formed over the oxide semiconductor, and then the insulator **282** is formed. After that, heat treatment is preferably performed. Specifically, the heat treatment is performed at 350° C. or higher, preferably 400° C. or higher under an oxygen-containing atmosphere, a nitrogen-containing atmosphere, or a mixed atmosphere of oxygen and nitrogen. The heat treatment is performed for one hour or more, preferably four hours or more, further preferably eight hours or more.

(536) The heat treatment enables outward diffusion of hydrogen in the oxide semiconductor through the insulator **280** and the insulator **282**. That is, the absolute amount of hydrogen in and near the oxide semiconductor can be reduced.

(537) The insulator **283** is formed after the heat treatment. The insulator **283** is a material having a function of a high blocking property against hydrogen, and thus can inhibit entry of hydrogen that has diffused outward or external hydrogen into the inside, specifically, to the oxide semiconductor side or the insulator **280** side.

(538) An example where the heat treatment is performed after the insulator **282** is formed is shown; however, one embodiment of the present invention is not limited thereto. For example, the heat treatment may be performed after the transistor layer **413** is formed or after the memory device layer **415_1** to the memory device layer **415_3** are formed. When hydrogen diffuses outward by the heat treatment, hydrogen diffuses to above the transistor layer **413** or in a lateral direction.

Similarly, in the case where heat treatment is performed after the memory device layer **415_1** to the memory device layer **415_3** are formed, hydrogen diffuses upward or in the lateral direction.

(539) Through the above manufacturing process, the insulator **214** and the insulator **283** are bonded, whereby the above-described sealing structure is formed.

(540) With the above structure and the above manufacturing process, a semiconductor device using an oxide semiconductor with reduced hydrogen concentration can be provided. Accordingly, a semiconductor device with high reliability can be provided. One embodiment of the present invention can provide a semiconductor device with favorable electrical characteristics.

(541) The structure, method, and the like described in this embodiment can be used in an appropriate combination with other structures, methods, and the like described in this embodiment, the other embodiments, or Examples.

Embodiment 3

(542) In this embodiment, a storage device including a transistor in which an oxide is used as a semiconductor (hereinafter, sometimes referred to as an OS transistor) and a capacitor (hereinafter, sometimes referred to as an OS memory device) of one embodiment of the present invention is described with reference to FIG. **34A**, FIG. **34B**, and FIG. **35A** to FIG. **35H**. The OS memory device is a storage device that includes at least a capacitor and an OS transistor that controls the charging and discharging of the capacitor. Since the OS transistor has an extremely low off-state current, the OS memory device has excellent retention characteristics and thus can function as a nonvolatile memory.

(543) <Structure Example of Storage Device>

(544) FIG. **34A** illustrates a structure example of the OS memory device. A storage device **1400** includes a peripheral circuit **1411** and a memory cell array **1470**. The peripheral circuit **1411**

includes a row circuit **1420**, a column circuit **1430**, an output circuit **1440**, and a control logic circuit **1460**.

(545) The column circuit **1430** includes, for example, a column decoder, a precharge circuit, a sense amplifier, a write circuit, and the like. The precharge circuit has a function of precharging wirings. The sense amplifier has a function of amplifying a data signal read from a memory cell. Note that the wirings are connected to the memory cell included in the memory cell array **1470**, and are described later in detail. The amplified data signal is output as a data signal RDATA to the outside of the storage device **1400** through the output circuit **1440**. The row circuit **1420** includes, for example, a row decoder and a word line driver circuit, and can select a row to be accessed.

(546) As power supply voltages from the outside, a low power supply voltage (VSS), a high power supply voltage (VDD) for the peripheral circuit **1411**, and a high power supply voltage (VIL) for the memory cell array **1470** are supplied to the storage device **1400**. Control signals (CE, WE, and RE), an address signal ADDR, and a data signal WDATA are also input to the storage device **1400** from the outside. The address signal ADDR is input to the row decoder and the column decoder, and the data signal WDATA is input to the write circuit.

(547) The control logic circuit **1460** processes the control signals (CE, WE, and RE) input from the outside, and generates control signals for the row decoder and the column decoder. The control signal CE is a chip enable signal, the control signal WE is a write enable signal, and the control signal RE is a read enable signal. Signals processed by the control logic circuit **1460** are not limited thereto, and other control signals are input as necessary.

(548) The memory cell array **1470** includes a plurality of memory cells MC arranged in a matrix and a plurality of wirings. Note that the number of wirings that connect the memory cell array **1470** to the row circuit **1420** depends on the structure of the memory cell MC, the number of memory cells MC in a column, and the like. The number of wirings that connect the memory cell array **1470** to the column circuit **1430** depends on the structure of the memory cell MC, the number of memory cells MC in a row, and the like.

(549) Note that FIG. 34A illustrates an example in which the peripheral circuit **1411** and the memory cell array **1470** are formed on the same plane; however, this embodiment is not limited thereto. For example, as illustrated in FIG. 34B, the memory cell array **1470** may be provided to overlap part of the peripheral circuit **1411**. For example, the sense amplifier may be provided below the memory cell array **1470** so that they overlap each other.

(550) FIG. 35A to FIG. 35H illustrate structure examples of a memory cell that can be used as the memory cell MC.

(551) [DOSRAM]

(552) FIG. 35A to FIG. 35C illustrate circuit structure examples of a memory cell of a DRAM. In this specification and the like, a DRAM using a memory cell including one OS transistor and one capacitor is referred to as a DOSRAM (Dynamic Oxide Semiconductor Random Access Memory) (registered trademark) in some cases. A memory cell **1471** illustrated in FIG. 35A includes a transistor M1 and a capacitor CA. Note that the transistor M1 includes a gate (sometimes referred to as a top gate) and a back gate.

(553) A first terminal of the transistor M1 is connected to a first terminal of the capacitor CA. A second terminal of the transistor M1 is connected to a wiring BIL. The gate of the transistor M1 is connected to a wiring WOL. The back gate of the transistor M1 is connected to a wiring BGL. A second terminal of the capacitor CA is connected to a wiring LL.

(554) The wiring BIL functions as a bit line, and the wiring WOL functions as a word line. The wiring LL functions as a wiring for applying a predetermined potential to the second terminal of the capacitor CA. In the time of data writing and data reading, a wiring LL may be at a ground potential or a low-level potential. The wiring BGL functions as a wiring for applying a potential to the back gate of the transistor M1. When a given potential is applied to the wiring BGL, the threshold voltage of the transistor M1 can be increased or decreased.

(555) Here, a memory cell **1471** illustrated in FIG. 35A corresponds to the storage device illustrated in FIG. 30A and FIG. 30B. That is, the transistor **M1** and the capacitor **CA** correspond to the transistor **200** and the capacitor device **292**, respectively.

(556) The circuit structure of the memory cell **MC** is not limited to that of the memory cell **1471**, and the circuit structure can be changed. For example, as in a memory cell **1472** illustrated in FIG. 35B, the back gate of the transistor **M1** may be connected not to the wiring **BGL** but to the wiring **WOL** in the memory cell **MC**. Alternatively, for example, the transistor **M1** may be a single-gate transistor, that is, a transistor without a back gate in the memory cell **MC** as in a memory cell **1473** illustrated in FIG. 35C.

(557) In the case where the semiconductor device described in any of the above embodiments is used in the memory cell **1471** and the like, the transistor **200** can be used as the transistor **M1**, and the capacitor **100** can be used as the capacitor **CA**. When an OS transistor is used as the transistor **M1**, the leakage current of the transistor **M1** can be extremely low. That is, with the use of the transistor **M1**, written data can be retained for a long time, and thus the frequency of the refresh operation for the memory cell can be decreased. Alternatively, refresh operation for the memory cell can be omitted. In addition, since the transistor **M1** has an extremely low leakage current, multi-level data or analog data can be retained in the memory cell **1471**, the memory cell **1472**, and the memory cell **1473**.

(558) In the DOSRAM, when the sense amplifier is provided below the memory cell array **1470** so that they overlap each other as described above, the bit line can be shortened. This reduces bit line capacitance, which can reduce the storage capacitance of the memory cell.

(559) [NOSRAM]

(560) FIG. 35D to FIG. 35G each illustrate a circuit structure example of a gain-cell memory cell including two transistors and one capacitor. A memory cell **1474** illustrated in FIG. 35D includes a transistor **M2**, a transistor **M3**, and a capacitor **CB**. Note that the transistor **M2** includes a top gate (simply referred to as a gate in some cases) and a back gate. In this specification and the like, a storage device including a gain-cell memory cell using an OS transistor as the transistor **M2** is referred to as a NOSRAM (Nonvolatile Oxide Semiconductor RAM) (registered trademark) in some cases.

(561) A first terminal of the transistor **M2** is connected to a first terminal of the capacitor **CB**. A second terminal of the transistor **M2** is connected to a wiring **WBL**. The gate of the transistor **M2** is connected to the wiring **WOL**. The back gate of the transistor **M2** is connected to the wiring **BGL**. A second terminal of the capacitor **CB** is connected to the wiring **CAL**. A first terminal of the transistor **M3** is connected to a wiring **RBL**. A second terminal of the transistor **M3** is connected to a wiring **SL**. A gate of the transistor **M3** is connected to the first terminal of the capacitor **CB**.

(562) The wiring **WBL** functions as a write bit line, the wiring **RBL** functions as a read bit line, and the wiring **WOL** functions as a word line. The wiring **CAL** functions as a wiring for applying a predetermined potential to the second terminal of the capacitor **CB**. In the time of data writing and data reading, a high-level potential is preferably applied to the wiring **CAL**. In the time of data retaining, a low-level potential is preferably applied to the wiring **CAL**. The wiring **BGL** functions as a wiring for applying a potential to the back gate of the transistor **M2**. The threshold voltage of the transistor **M2** can be increased or decreased by applying a given potential to the wiring **BGL**.

(563) Here, the memory cell **1474** illustrated in FIG. 35D corresponds to the storage device illustrated in FIG. 28 and FIG. 29. That is, the transistor **M2**, the capacitor **CB**, the transistor **M3**, the wiring **WBL**, the wiring **WOL**, the wiring **BGL**, the wiring **CAL**, the wiring **RBL**, and the wiring **SL** correspond to the transistor **200**, the capacitor **100**, the transistor **300**, the wiring **1003**, the wiring **1004**, the wiring **1006**, the wiring **1005**, the wiring **1002**, and the wiring **1001**, respectively.

(564) The circuit structure of the memory cell **MC** is not limited to that of the memory cell **1474**, and the circuit structure can be changed as appropriate. For example, as in a memory cell **1475**

illustrated in FIG. 35E, the back gate of the transistor M2 may be connected not to the wiring BGL but to the wiring WOL in the memory cell MC. Alternatively, for example, the transistor M2 may be a single-gate transistor, that is, a transistor without a back gate in the memory cell MC as in a memory cell 1476 illustrated in FIG. 35F. For example, the memory cell MC may have a structure in which the wiring WBL and the wiring RBL are combined into one wiring BIL as in a memory cell 1477 illustrated in FIG. 35G.

(565) In the case where the semiconductor device described in any of the above embodiments is used in the memory cell 1474 and the like, the transistor 200 can be used as the transistor M2, the transistor 300 can be used as the transistor M3, and the capacitor 100 can be used as the capacitor CB. When an OS transistor is used as the transistor M2, the leakage current of the transistor M2 can be extremely low. Consequently, with the use of the transistor M2, written data can be retained for a long time, and thus the frequency of the refresh operation for the memory cell can be decreased. Alternatively, refresh operation for the memory cell can be omitted. In addition, since the transistor M2 has an extremely low leakage current, multi-level data or analog data can be retained in the memory cell 1474. The same applies to the memory cell 1475 to the memory cell 1477.

(566) Note that the transistor M3 may be a transistor containing silicon in a channel formation region (hereinafter, sometimes referred to as a Si transistor). The Si transistor may be either an n-channel transistor or a p-channel transistor. A Si transistor has higher field-effect mobility than an OS transistor in some cases. Therefore, a Si transistor may be used as the transistor M3 functioning as a reading transistor. Furthermore, the transistor M2 can be stacked over the transistor M3 when a Si transistor is used as the transistor M3, in which case the area occupied by the memory cell can be reduced, leading to high integration of the storage device.

(567) Alternatively, the transistor M3 may be an OS transistor. When an OS transistor is used as each of the transistor M2 and the transistor M3, the circuit of the memory cell array 1470 can be formed using only n-channel transistors.

(568) FIG. 35H illustrates an example of a gain-cell memory cell including three transistors and one capacitor. A memory cell 1478 illustrated in FIG. 35H includes a transistor M4 to a transistor M6 and a capacitor CC. The capacitor CC is provided as appropriate. The memory cell 1478 is electrically connected to the wiring BIL, a wiring RWL, a wiring WWL, the wiring BGL, and a wiring GNDL. The wiring GNDL is a wiring for supplying a low-level potential. Note that the memory cell 1478 may be electrically connected to the wiring RBL and the wiring WBL instead of the wiring BIL.

(569) The transistor M4 is an OS transistor with a back gate, and the back gate is electrically connected to the wiring BGL. Note that the back gate and the gate of the transistor M4 may be electrically connected to each other. Alternatively, the transistor M4 does not necessarily include the back gate.

(570) Note that each of the transistor M5 and the transistor M6 may be an n-channel Si transistor or a p-channel Si transistor. Alternatively, the transistor M4 to the transistor M6 may be OS transistors. In that case, the circuit of the memory cell array 1470 can be formed using only n-channel transistors.

(571) In the case where the semiconductor device described in any of the above embodiments is used in the memory cell 1478, the transistor 200 can be used as the transistor M4, the transistor 300 can be used as the transistor M5 and the transistor M6, and the capacitor 100 can be used as the capacitor CC. When an OS transistor is used as the transistor M4, the leakage current of the transistor M4 can be extremely low.

(572) Note that the structures of the peripheral circuit 1411, the memory cell array 1470, and the like described in this embodiment are not limited to the above. The arrangement and functions of these circuits and the wirings, circuit components, and the like connected to the circuits can be changed, removed, or added as needed.

(573) The storage device of one embodiment of the present invention operates fast and can retain data for a long time.

(574) The structure, method, and the like described in this embodiment can be used in an appropriate combination with other structures, methods, and the like described in this embodiment, the other embodiments, or Examples.

Embodiment 4

(575) In this embodiment, an example of a chip **1200** on which the semiconductor device of the present invention is mounted is described with reference to FIG. **36A** and FIG. **36B**. A plurality of circuits (systems) are mounted on the chip **1200**. A technique for integrating a plurality of circuits (systems) into one chip is referred to as system on chip (SoC) in some cases.

(576) As shown in FIG. **36A**, the chip **1200** includes a CPU **1211**, a GPU **1212**, one or more analog arithmetic units **1213**, one or more memory controllers **1214**, one or more interfaces **1215**, one or more network circuits **1216**, and the like.

(577) A bump (not illustrated) is provided on the chip **1200**, and as illustrated in FIG. **36B**, the chip **1200** is connected to a first surface of a printed circuit board (PCB) **1201**. In addition, a plurality of bumps **1202** are provided on a rear side of the first surface of the PCB **1201**, and the PCB **1201** is connected to a motherboard **1203**.

(578) Storage devices such as DRAMs **1221** and a flash memory **1222** may be provided over the motherboard **1203**. For example, the DOSRAM described in the above embodiment can be used as the DRAM **1221**. In addition, for example, the NOSRAM described in the above embodiment can be used as the flash memory **1222**.

(579) The CPU **1211** preferably includes a plurality of CPU cores. In addition, the GPU **1212** preferably includes a plurality of GPU cores. Furthermore, the CPU **1211** and the GPU **1212** may each include a memory for temporarily storing data. Alternatively, a common memory for the CPU **1211** and the GPU **1212** may be provided in the chip **1200**. The NOSRAM or the DOSRAM described above can be used as the memory. Moreover, the GPU **1212** is suitable for parallel computation of a number of data and thus can be used for image processing or product-sum operation. When an image processing circuit or a product-sum operation circuit using an oxide semiconductor of the present invention is provided in the GPU **1212**, image processing and product-sum operation can be performed with low power consumption.

(580) In addition, since the CPU **1211** and the GPU **1212** are provided on the same chip, a wiring between the CPU **1211** and the GPU **1212** can be shortened, and the data transfer from the CPU **1211** to the GPU **1212**, the data transfer between the memories included in the CPU **1211** and the GPU **1212**, and the transfer of arithmetic operation results from the GPU **1212** to the CPU **1211** after the arithmetic operation in the GPU **1212** can be performed at high speed.

(581) The analog arithmetic unit **1213** includes one or both of an A/D (analog/digital) converter circuit and a D/A (digital/analog) converter circuit. Furthermore, the product-sum operation circuit may be provided in the analog arithmetic unit **1213**.

(582) The memory controller **1214** includes a circuit functioning as a controller of the DRAM **1221** and a circuit functioning as an interface of the flash memory **1222**.

(583) The interface **1215** includes an interface circuit for an external connection device such as a display device, a speaker, a microphone, a camera, or a controller. Examples of the controller include a mouse, a keyboard, and a game controller. As such an interface, a USB (Universal Serial Bus), an HDMI (registered trademark) (High-Definition Multimedia Interface), or the like can be used.

(584) The network circuit **1216** includes a network circuit such as a LAN (Local Area Network). The network circuit **1216** may further include a circuit for network security.

(585) The circuits (systems) can be formed in the chip **1200** through the same manufacturing process. Therefore, even when the number of circuits needed for the chip **1200** increases, there is no need to increase the number of steps in the manufacturing process; thus, the chip **1200** can be

manufactured at low cost.

(586) The motherboard **1203** provided with the PCB **1201** on which the chip **1200** including the GPU **1212** is mounted, the DRAMs **1221**, and the flash memory **1222** can be referred to as a GPU module **1204**.

(587) The GPU module **1204** includes the chip **1200** using SoC technology, and thus can have a small size. In addition, the GPU module **1204** is excellent in image processing, and thus is suitably used in a portable electronic device such as a smartphone, a tablet terminal, a laptop PC, or a portable (mobile) game machine. Furthermore, the product-sum operation circuit using the GPU **1212** can perform a method such as a deep neural network (DNN), a convolutional neural network (CNN), a recurrent neural network (RNN), an autoencoder, a deep Boltzmann machine (DBM), or a deep belief network (DBN); hence, the chip **1200** can be used as an AI chip or the GPU module **1204** can be used as an AI system module.

(588) The structure, method, and the like described in this embodiment can be used in an appropriate combination with other structures, methods, and the like described in this embodiment, the other embodiments, or Examples.

Embodiment 5

(589) In this embodiment, examples of electronic components and electronic devices in which the storage device or the like described in the above embodiment is incorporated are described.

(590) <Electronic Component>

(591) First, FIG. **37A** and FIG. **37B** illustrate examples of an electronic component including a storage device **720**.

(592) FIG. **37A** is a perspective view of an electronic component **700** and a substrate (circuit board **704**) on which the electronic component **700** is mounted. The electronic component **700** in FIG. **37A** includes the storage device **720** in a mold **711**. FIG. **37A** omits part of the electronic component to show the inside of the electronic component **700**. The electronic component **700** includes a land **712** outside the mold **711**. The land **712** is electrically connected to an electrode pad **713**, and the electrode pad **713** is electrically connected to the storage device **720** via a wire **714**. The electronic component **700** is mounted on a printed circuit board **702**, for example. A plurality of such electronic components are combined and electrically connected to each other on the printed circuit board **702**, which forms the circuit board **704**.

(593) The storage device **720** includes a driver circuit layer **721** and a storage circuit layer **722**.

(594) FIG. **37B** is a perspective view of an electronic component **730**. The electronic component **730** is an example of a SiP (System in Package) or an MCM (Multi Chip Module). In the electronic component **730**, an interposer **731** is provided over a package substrate **732** (printed circuit board) and a semiconductor device **735** and a plurality of storage devices **720** are provided over the interposer **731**.

(595) The electronic component **730** using the storage device **720** as a high bandwidth memory (HBM) is illustrated as an example. An integrated circuit (a semiconductor device) such as a CPU, a GPU, or an FPGA can be used as the semiconductor device **735**.

(596) As the package substrate **732**, a ceramic substrate, a plastic substrate, a glass epoxy substrate, or the like can be used. As the interposer **731**, a silicon interposer, a resin interposer, or the like can be used.

(597) The interposer **731** includes a plurality of wirings and has a function of electrically connecting a plurality of integrated circuits with different terminal pitches. The plurality of wirings have a single-layer structure or a layered structure. The interposer **731** has a function of electrically connecting an integrated circuit provided on the interposer **731** to an electrode provided on the package substrate **732**. Accordingly, the interposer is sometimes referred to as a “redistribution substrate” or an “intermediate substrate”. A through electrode may be provided in the interposer **731** to be used for electrically connecting the integrated circuit and the package substrate **732**. In the case of using a silicon interposer, a through-silicon via (TSV) can also be used as the through

electrode.

(598) A silicon interposer is preferably used as the interposer **731**. The silicon interposer can be manufactured at lower cost than an integrated circuit because it is not necessary to provide an active element. Moreover, since wirings of the silicon interposer can be formed through a semiconductor process, the formation of minute wirings, which is difficult for a resin interposer, is easily achieved.

(599) An HBM needs to be connected to many wirings to achieve a wide memory bandwidth. Therefore, an interposer on which an HBM is mounted requires minute and densely formed wirings. For this reason, a silicon interposer is preferably used as the interposer on which an HBM is mounted.

(600) In a SiP, an MCM, or the like using a silicon interposer, a decrease in reliability due to a difference in expansion coefficient between an integrated circuit and the interposer is less likely to occur. Furthermore, a surface of a silicon interposer has high planarity, and a poor connection between the silicon interposer and an integrated circuit provided thereon is less likely to occur. It is particularly preferable to use a silicon interposer for a 2.5D package (2.5D mounting) in which a plurality of integrated circuits are arranged side by side on the interposer.

(601) A heat sink (radiator plate) may be provided to overlap the electronic component **730**. In the case of providing a heat sink, the heights of integrated circuits provided on the interposer **731** are preferably equal to each other. In the electronic component **730** of this embodiment, the heights of the storage device **720** and the semiconductor device **735** are preferably equal to each other, for example.

(602) An electrode **733** may be provided on the bottom portion of the package substrate **732** to mount the electronic component **730** on another substrate. FIG. **37B** illustrates an example in which the electrode **733** is formed of a solder ball. Solder balls are provided in a matrix on the bottom portion of the package substrate **732**, whereby a BGA (Ball Grid Array) can be achieved. Alternatively, the electrode **733** may be formed of a conductive pin. When conductive pins are provided in a matrix on the bottom portion of the package substrate **732**, a PGA (Pin Grid Array) can be achieved.

(603) The electronic component **730** can be mounted on another substrate by various mounting methods not limited to BGA and PGA. For example, a mounting method such as SPGA (Staggered Pin Grid Array), LGA (Land Grid Array), QFP (Quad Flat Package), QFJ (Quad Flat J-leaded package), or QFN (Quad Flat Non-leaded package) can be employed.

(604) The structure, method, and the like described in this embodiment can be used in an appropriate combination with other structures, methods, and the like described in this embodiment, the other embodiments, or Examples.

Embodiment 6

(605) In this embodiment, application examples of the storage device using the semiconductor device described in the above embodiment are described. The semiconductor device described in the above embodiment can be applied to, for example, storage devices of a variety of electronic devices (e.g., information terminals, computers, smartphones, e-book readers, digital cameras (including video cameras), video recording/reproducing devices, and navigation systems). Here, the computers refer not only to tablet computers, notebook computers, and desktop computers, but also to large computers such as server systems. Alternatively, the semiconductor device described in the above embodiment is applied to a variety of removable storage devices such as memory cards (e.g., SD cards), USB memories, and SSDs (solid state drives). FIG. **38A** to FIG. **38E** schematically illustrate some structure examples of removable storage devices. The semiconductor device described in the above embodiment is processed into a packaged memory chip and used in a variety of storage devices and removable memories, for example.

(606) FIG. **38A** is a schematic view of a USB memory. A USB memory **1100** includes a housing **1101**, a cap **1102**, a USB connector **1103**, and a substrate **1104**. The substrate **1104** is held in the

housing **1101**. The substrate **1104** is provided with a memory chip **1105** and a controller chip **1106**, for example. The semiconductor device described in the above embodiment can be incorporated in the memory chip **1105** or the like.

(607) FIG. **38B** is a schematic external view of an SD card, and FIG. **38C** is a schematic view of the internal structure of the SD card. An SD card **1110** includes a housing **1111**, a connector **1112**, and a substrate **1113**. The substrate **1113** is held in the housing **1111**. The substrate **1113** is provided with a memory chip **1114** and a controller chip **1115**, for example. When the memory chip **1114** is also provided on the back side of the substrate **1113**, the capacity of the SD card **1110** can be increased. In addition, a wireless chip with a radio communication function may be provided on the substrate **1113**. With this, data can be read from and written in the memory chip **1114** by radio communication between a host device and the SD card **1110**. The semiconductor device described in the above embodiment can be incorporated in the memory chip **1114** or the like.

(608) FIG. **38D** is a schematic external view of an SSD, and FIG. **38E** is a schematic view of the internal structure of the SSD. An SSD **1150** includes a housing **1151**, a connector **1152**, and a substrate **1153**. The substrate **1153** is held in the housing **1151**. The substrate **1153** is provided with a memory chip **1154**, a memory chip **1155**, and a controller chip **1156**, for example. The memory chip **1155** is a work memory of the controller chip **1156**, and a DOSRAM chip can be used, for example. When the memory chip **1154** is also provided on the back side of the substrate **1153**, the capacity of the SSD **1150** can be increased. The semiconductor device described in the above embodiment can be incorporated in the memory chip **1154** or the like.

(609) The structure, method, and the like described in this embodiment can be used in an appropriate combination with other structures, methods, and the like described in this embodiment, the other embodiments, or Examples.

Embodiment 7

(610) The semiconductor device of one embodiment of the present invention can be used as a processor such as a CPU and a GPU or a chip. FIG. **39A** to FIG. **39H** illustrate specific examples of electronic devices including a chip or a processor such as a CPU or a GPU of one embodiment of the present invention.

(611) <Electronic Device and System>

(612) The GPU or the chip of one embodiment of the present invention can be mounted on a variety of electronic devices. Examples of electronic devices include a digital camera, a digital video camera, a digital photo frame, an e-book reader, a mobile phone, a portable game machine, a portable information terminal, and an audio reproducing device in addition to electronic devices provided with a relatively large screen, such as a television device, a monitor for a desktop or notebook information terminal or the like, digital signage, and a large game machine like a pachinko machine. When the GPU or the chip of one embodiment of the present invention is provided in the electronic device, the electronic device can include artificial intelligence.

(613) The electronic device of one embodiment of the present invention may include an antenna. When a signal is received by the antenna, the electronic device can display a video, data, or the like on a display portion. When the electronic device includes the antenna and a secondary battery, the antenna may be used for contactless power transmission.

(614) The electronic device of one embodiment of the present invention may include a sensor (a sensor having a function of measuring force, displacement, position, speed, acceleration, angular velocity, rotational frequency, distance, light, liquid, magnetism, temperature, a chemical substance, sound, time, hardness, an electric field, current, voltage, power, radioactive rays, flow rate, humidity, a gradient, oscillation, odor, or infrared rays).

(615) The electronic device of one embodiment of the present invention can have a variety of functions. For example, the electronic device can have a function of displaying a variety of data (a still image, a moving image, a text image, and the like) on the display portion, a touch panel function, a function of displaying a calendar, date, time, and the like, a function of executing a

variety of software (programs), a wireless communication function, and a function of reading out a program or data stored in a recording medium. FIG. 39A to FIG. 39H illustrate examples of electronic devices.

(616) [Information Terminal]

(617) FIG. 39A illustrates a mobile phone (smartphone), which is a type of information terminal. An information terminal **5100** includes a housing **5101** and a display portion **5102**. As input interfaces, a touch panel is provided in the display portion **5102** and a button is provided in the housing **5101**.

(618) When the chip of one embodiment of the present invention is applied to the information terminal **5100**, the information terminal **5100** can execute an application utilizing artificial intelligence. Examples of the application utilizing artificial intelligence include an application for recognizing a conversation and displaying the content of the conversation on the display portion **5102**; an application for recognizing letters, figures, and the like input to the touch panel of the display portion **5102** by a user and displaying them on the display portion **5102**; and an application for performing biometric authentication using fingerprints, voice prints, or the like.

(619) FIG. 39B illustrates a notebook information terminal **5200**. The notebook information terminal **5200** includes a main body **5201** of the information terminal, a display portion **5202**, and a keyboard **5203**.

(620) Like the information terminal **5100** described above, when the chip of one embodiment of the present invention is applied to the notebook information terminal **5200**, the notebook information terminal **5200** can execute an application utilizing artificial intelligence. Examples of the application utilizing artificial intelligence include design-support software, text correction software, and software for automatic menu generation. Furthermore, with the use of the notebook information terminal **5200**, novel artificial intelligence can be developed.

(621) Note that although FIG. 39A and FIG. 39B illustrate a smartphone and a notebook information terminal, respectively, as examples of the electronic device in the above description, an information terminal other than a smartphone and a notebook information terminal can be used. Examples of information terminals other than a smartphone and a notebook information terminal include a PDA (Personal Digital Assistant), a desktop information terminal, and a workstation.

(622) [Game Machines]

(623) FIG. 39C illustrates a portable game machine **5300** as an example of a game machine. The portable game machine **5300** includes a housing **5301**, a housing **5302**, a housing **5303**, a display portion **5304**, a connection portion **5305**, an operation key **5306**, and the like. The housing **5302** and the housing **5303** can be detached from the housing **5301**. When the connection portion **5305** provided in the housing **5301** is attached to another housing (not illustrated), an image to be output to the display portion **5304** can be output to another video device (not illustrated). In that case, the housing **5302** and the housing **5303** can each function as an operating unit. Thus, a plurality of players can play a game at the same time. The chip described in the above embodiment can be incorporated into the chip provided on a substrate in the housing **5301**, the housing **5302** and the housing **5303**.

(624) FIG. 39D illustrates a stationary game machine **5400** as an example of a game machine. A controller **5402** is wired or connected wirelessly to the stationary game machine **5400**.

(625) Using the GPU or the chip of one embodiment of the present invention in a game machine such as the portable game machine **5300** and the stationary game machine **5400** achieves a low-power-consumption game machine. Moreover, heat generation from a circuit can be reduced owing to low power consumption; thus, the influence of heat generation on the circuit, a peripheral circuit, and a module can be reduced.

(626) Furthermore, when the GPU or the chip of one embodiment of the present invention is applied to the portable game machine **5300**, the portable game machine **5300** including AI can be achieved.

(627) In general, the progress of a game, the actions and words of game characters, and expressions of an event and the like occurring in the game are determined by the program in the game; however, the use of artificial intelligence in the portable game machine **5300** enables expressions not limited by the game program. For example, it becomes possible to change expressions such as questions posed by the player, the progress of the game, time, and actions and words of game characters.

(628) In addition, when a game requiring a plurality of players is played on the portable game machine **5300**, the artificial intelligence can create a virtual game player; thus, the game can be played alone with the game player created by the artificial intelligence as an opponent.

(629) Although the portable game machine and the stationary game machine are illustrated as examples of game machines in FIG. **39C** and FIG. **39D**, the game machine using the GPU or the chip of one embodiment of the present invention is not limited thereto. Examples of the game machine to which the GPU or the chip of one embodiment of the present invention is applied include an arcade game machine installed in entertainment facilities (a game center, an amusement park, and the like), and a throwing machine for batting practice installed in sports facilities.

(630) [Large Computer]

(631) The GPU or the chip of one embodiment of the present invention can be used in a large computer.

(632) FIG. **39E** illustrates a supercomputer **5500** as an example of a large computer. FIG. **39F** illustrates a rack-mount computer **5502** included in the supercomputer **5500**.

(633) The supercomputer **5500** includes a rack **5501** and a plurality of rack-mount computers **5502**. The plurality of computers **5502** are stored in the rack **5501**. The computer **5502** includes a plurality of substrates **5504** on which the GPU or the chip shown in the above embodiment can be mounted.

(634) The supercomputer **5500** is a large computer mainly used for scientific computation. In scientific computation, an enormous amount of arithmetic operation needs to be processed at a high speed; hence, power consumption is large and chips generate a large amount of heat. Using the GPU or the chip of one embodiment of the present invention in the supercomputer **5500** achieves a low-power-consumption supercomputer. Moreover, heat generation from a circuit can be reduced owing to low power consumption; thus, the influence of heat generation on the circuit, a peripheral circuit, and a module can be reduced.

(635) Although a supercomputer is illustrated as an example of a large computer in FIG. **39E** and FIG. **39F**, a large computer using the GPU or the chip of one embodiment of the present invention is not limited thereto. Other examples of large computers in which the GPU or the chip of one embodiment of the present invention is usable include a computer that provides service (a server) and a large general-purpose computer (a mainframe).

(636) [Moving Vehicle]

(637) The GPU or the chip of one embodiment of the present invention can be applied to an automobile, which is a moving vehicle, and the periphery of a driver's seat in the automobile.

(638) FIG. **39G** illustrates an area around a windshield inside an automobile, which is an example of a moving vehicle. FIG. **39G** illustrates a display panel **5701**, a display panel **5702**, and a display panel **5703** that are attached to a dashboard and a display panel **5704** that is attached to a pillar.

(639) The display panel **5701** to the display panel **5703** can provide a variety of kinds of information by displaying a speedometer, a tachometer, mileage, a fuel gauge, a gear state, air-condition setting, and the like. In addition, the content, layout, or the like of the display on the display panels can be changed as appropriate to suit the user's preference, so that the design quality can be increased. The display panel **5701** to the display panel **5703** can also be used as lighting devices.

(640) The display panel **5704** can compensate for view obstructed by the pillar (a blind spot) by showing an image taken by an imaging device (not illustrated) provided for the automobile. That is,

displaying an image taken by the imaging device provided outside the automobile leads to compensation for the blind spot and an increase in safety. In addition, displaying an image to compensate for a portion that cannot be seen makes it possible for the driver to confirm the safety more naturally and comfortably. The display panel **5704** can also be used as a lighting device. (641) Since the GPU or the chip of one embodiment of the present invention can be applied to a component of artificial intelligence, the chip can be used for an automatic driving system of the automobile, for example. The chip can also be used for a system for navigation, risk prediction, or the like. A structure may be employed in which the display panel **5701** to the display panel **5704** display navigation information, risk prediction information, or the like.

(642) Note that although an automobile is described above as an example of a moving vehicle, the moving vehicle is not limited to an automobile. Examples of the moving vehicle include a train, a monorail train, a ship, and a flying vehicle (a helicopter, an unmanned aircraft (a drone), an airplane, and a rocket), and these moving vehicles can each include a system utilizing artificial intelligence when the chip of one embodiment of the present invention is applied to each of these moving vehicles.

(643) [Household Appliance]

(644) FIG. **39H** illustrates an electric refrigerator-freezer **5800** as an example of a household appliance. The electric refrigerator-freezer **5800** includes a housing **5801**, a refrigerator door **5802**, a freezer door **5803**, and the like.

(645) When the chip of one embodiment of the present invention is applied to the electric refrigerator-freezer **5800**, the electric refrigerator-freezer **5800** including artificial intelligence can be achieved. Utilizing the artificial intelligence enables the electric refrigerator-freezer **5800** to have a function of automatically making a menu based on foods stored in the electric refrigerator-freezer **5800**, expiration dates of the foods, or the like, a function of automatically adjusting temperature to be appropriate for the foods stored in the electric refrigerator-freezer **5800**, and the like.

(646) Although the electric refrigerator-freezer is described in this example as a household appliance, examples of other household appliances include a vacuum cleaner, a microwave oven, an electric oven, a rice cooker, a water heater, an IH cooker, a water server, a heating-cooling combination appliance such as an air conditioner, a washing machine, a drying machine, and an audio visual appliance.

(647) The electronic devices, the functions of the electronic devices, the application examples of artificial intelligence, their effects, and the like described in this embodiment can be combined as appropriate with the description of another electronic device.

(648) The structure, method, and the like described in this embodiment can be used in an appropriate combination with other structures, methods, and the like described in this embodiment, the other embodiments, or Examples.

Example 1

(649) In this example, silicon oxide was deposited by a PEALD method using SiH₄ as a gas (precursor) containing silicon but not containing hydrocarbon and N₂O as a reactant, and an ALD Window was evaluated.

(650) An ALD Window is described below with reference to FIG. **40**. FIG. **40** is a diagram showing an ALD Window, and the vertical axis represents GPC (Growth Per Cycle) that is the thickness of a film deposited in one cycle, and the horizontal axis represents substrate temperature. In addition, straight lines in FIG. **40** represent behavior examples of the GPC at the time when only deposition temperature was changed and the introduction time of a precursor and the purge time are not changed. As shown in FIG. **40**, the GPC shows increase behavior and decrease behavior on the low temperature side and the high temperature side. Specifically, the straight line denoted by A in FIG. **40** represents a region in which adsorption of the precursor to a substrate is not saturated and the GPC increases with an increase in the substrate temperature. The straight line denoted by C

represents a region in which adsorption of the precursor to the substrate is extracted with an increase in the substrate temperature and the GPC decreases. The straight line denoted by D is influenced by physical adsorption of the precursor and depends on a material of the precursor. In addition, the straight line denoted by E is due to the decomposition reaction of the precursor on the substrate surface and depends on the material of the precursor. As described above, the increase and decrease behavior of the GPC depends on the surface reaction of the precursor or the adsorption of the precursor; as the straight line denoted by B, a region with less influence of the surface reaction or adsorption of the precursor and constant GPC is referred to as an ALD Window, which is a region at substrate temperature at which desired ALD deposition is performed.

(651) Next, a sample used for the evaluation of the ALD Window is described. For the sample, a silicon oxide was deposited over a silicon wafer by a PEALD method using SiH_4 as a precursor and N_2O as a reactant. Deposition was performed at substrate temperatures of 150° C., 200° C., 250° C., 300° C., 325° C., 350° C., 375° C., and 400° C. The steps shown in FIG. 5 and the sequence shown in FIG. 6B were used for the deposition at all of the substrate temperatures.

(652) FIG. 41 shows a diagram in which the GPC at each substrate temperature is plotted. The vertical axis represents the GPC [nm/cycle] and the horizontal axis represents the substrate temperature [° C.]. A tendency was observed in which the GPC increases by making the substrate temperature higher than 150° C., and the GPC is substantially constant and saturated at the substrate temperature from 300° C. to 400° C. According to the result, the substrate temperature from 300° C. to 400° C. is presumably the ALD Window.

(653) The structure described above in this example can be used in an appropriate combination with the other example or the other embodiments.

Example 2

(654) Then, a silicon oxide film was deposited at a substrate temperature of 350° C. that is in the temperature range of the ALD Window obtained in Example 1, and the coverage thereof was evaluated. For the coverage evaluation, a scanning transmission electron microscope (STEM) was used.

(655) A sample used for the coverage evaluation is described below. As the sample, the transistor **200** illustrated in FIG. 1 was manufactured by <Manufacturing method of semiconductor device> described in Embodiment 1. Note that the oxide **230a** is deposited by a sputtering method using an oxide target with In:Ga:Zn=1:3:4 [atomic ratio]. In addition, the oxide **230b** is deposited by a sputtering method using an oxide target with In:Ga:Zn=4:2:4.1 [atomic ratio].

(656) The insulator **250a** was deposited over the oxide **230** (the oxide **230a** and the oxide **230b**) by a PEALD method. For the insulator **250a**, a silicon oxide film was deposited at a substrate temperature of 350° C. that is in the temperature range of the ALD Window obtained in Example 1. The number of cycles of the sequence was 50. In the above manner, the sample was manufactured.

(657) The coverage was evaluated by STEM observation on a portion illustrated in FIG. 1C, i.e., a cross section of the channel formation region of the transistor **200** in the channel width direction.

(658) FIG. 42A is a STEM cross-sectional image. The thickness of the insulator **250a** in each portion (measurement point) of F to J added on the cross-sectional image was obtained by length measuring. FIG. 42B shows the thickness measurement results in the measurement points of F to J. According to the results, the thickness of the insulator **250a** in the portions of F to J was higher than or equal to 2.0 nm and less than or equal to 2.5 nm, and it was observed that variation of the thickness of the insulator **250a** is small. In particular, the thickness was 2.4 nm in each portion of F and J that is a position in which the insulator **250a** is in contact with the side surface of the oxide **230**, and excellent coverage was confirmed. Thus, by deposition in the temperature range of the ALD Window, a silicon oxide film with excellent coverage was obtained.

(659) The structure described above in this example can be used in an appropriate combination with the other example or the other embodiments.

REFERENCE NUMERALS

(660) **100**: capacitor, **110**: conductor, **112**: conductor, **115**: conductor, **120**: conductor, **125**: conductor, **130**: insulator, **140**: conductor, **142**: insulator, **145**: insulator, **150**: insulator, **152**: insulator, **153**: conductor, **154**: insulator, **156**: insulator, **200**: transistor, **200_n**: transistor, **200_1**: transistor, **200a**: transistor, **200b**: transistor, **200T**: transistor, **205**: conductor, **205a**: conductor, **205A**: conductive film, **205b**: conductor, **205B**: conductive film, **205c**: conductor, **205C**: conductive film, **210**: insulator, **212**: insulator, **214**: insulator, **216**: insulator, **217**: insulator, **218**: conductor, **222**: insulator, **224**: insulator, **230**: oxide, **230a**: oxide, **230A**: oxide film, **230b**: oxide, **230B**: oxide film, **230ba**: region, **230bb**: region, **230bc**: region, **240**: conductor, **240a**: conductor, **240b**: conductor, **241**: insulator, **241a**: insulator, **241b**: insulator, **242**: conductor, **242a**: conductor, **242A**: conductive film, **242b**: conductor, **242B**: conductive layer, **242c**: conductor, **243**: oxide, **243a**: oxide, **243A**: oxide film, **243b**: oxide, **243B**: oxide layer, **246**: conductor, **246a**: conductor, **246b**: conductor, **250**: insulator, **250a**: insulator, **250A**: insulating film, **250b**: insulator, **250B**: insulating film, **260**: conductor, **260a**: conductor, **260b**: conductor, **265**: sealing portion, **265a**: sealing portion, **265b**: sealing portion, **271**: insulator, **271a**: insulator, **271A**: insulating film, **271b**: insulator, **271B**: insulating layer, **271c**: insulator, **272**: insulator, **274**: insulator, **280**: insulator, **282**: insulator, **282a**: insulator, **282b**: insulator, **283**: insulator, **284**: insulator, **286**: insulator, **290**: memory device, **292**: capacitor device, **292a**: capacitor device, **292b**: capacitor device, **293**: insulator, **294**: conductor, **294a**: conductor, **294b**: conductor, **300**: transistor, **311**: substrate, **313**: semiconductor region, **314a**: low-resistance region, **314b**: low-resistance region, **315**: insulator, **316**: conductor, **320**: insulator, **322**: insulator, **324**: insulator, **326**: insulator, **328**: conductor, **330**: conductor, **350**: insulator, **352**: insulator, **354**: insulator, **356**: conductor, **401**: gas, **402**: oxidizing gas, **403**: high-frequency power, **411**: element layer, **413**: transistor layer, **415**: memory device layer, **415_1**: memory device layer, **415_3**: memory device layer, **415_4**: memory device layer, **420**: memory device, **424**: conductor, **440**: conductor, **470**: memory unit, **600**: semiconductor device, **601**: semiconductor device, **610**: cell array, **610_n**: cell array, **610_1**: cell array, **700**: electrical component, **702**: printed circuit board, **704**: circuit board, **711**: mold, **712**: land, **713**: electrode pad, **714**: wire, **720**: storage device, **721**: driver circuit layer, **722**: storage circuit layer, **730**: electrical component, **731**: interposer, **732**: package substrate, **733**: electrode, **735**: semiconductor device, **1001**: wiring, **1002**: wiring, **1003**: wiring, **1004**: wiring, **1005**: wiring, **1006**: wiring

Claims

1. A method for manufacturing a semiconductor device, comprising steps of: depositing a first insulator; depositing an oxide film over the first insulator; performing first heat treatment; depositing a first conductive film and a first insulating film in this order over the oxide film; processing the oxide film, the first conductive film, and the first insulating film into island shapes to form an oxide, a conductive layer, and an insulating layer; depositing a second insulator over the first insulator, the oxide, the conductive layer, and the insulating layer; depositing a third insulator over the second insulator; forming an opening in the conductive layer, the insulating layer, the second insulator, and the third insulator to form a first conductor and a second conductor from the conductive layer and a fourth insulator and a fifth insulator from the insulating layer; performing second heat treatment; depositing a second insulating film over the third insulator and the opening; depositing a third insulating film over the second insulating film; performing microwave treatment; depositing a second conductive film over the third insulating film; and performing CMP treatment on the second insulating film, the third insulating film, and the second conductive film to expose a top surface of the third insulator so that a sixth insulator, a seventh insulator, and a third conductor are formed, wherein the second insulating film is deposited by a PEALD method using a first gas containing silicon but not containing hydrocarbon and a second gas which is an oxidizing gas.

2. The method for manufacturing a semiconductor device according to claim 1, wherein the deposition of the second insulating film by the PEALD method comprising: first step of introducing the first gas and the second gas into a reaction chamber; a second step of stopping the introduction of the first gas and purging the first gas remaining in the reaction chamber; a third step of applying high-frequency power to generate plasma by using the second gas; and a fourth step of stopping the application of the high-frequency power, wherein the first step to the fourth step are regarded as one cycle, and wherein one cycle to 500 cycles are performed.
 3. The method for manufacturing a semiconductor device according to claim 1, wherein the first gas contains any one or more selected from SiH.sub.4, Si.sub.2H.sub.6, SiF.sub.4, SiC.sub.14, SiBr.sub.4, SiH.sub.2Cl.sub.2, and SiH.sub.2I.sub.2, and wherein the second gas contains any one or more selected from O.sub.2, O.sub.3, N.sub.2O, NO.sub.2, and H.sub.2O.
 4. The method for manufacturing a semiconductor device according to claim 1, wherein the first gas contains SiH.sub.4 and the second gas contains N.sub.2O.
 5. The method for manufacturing a semiconductor device according to claim 2, wherein a pressure in the reaction chamber in the first step is higher than or equal to 400 Pa and lower than or equal to 1000 Pa.
 6. The method for manufacturing a semiconductor device according to claim 1, wherein a temperature of the first heat treatment is higher than a temperature of the second heat treatment.
 7. A semiconductor device comprising: an oxide; a first conductor and a second conductor over the oxide, the first conductor functioning as one of a source electrode and a drain electrode, and the second conductor functioning as the other of the source electrode and the drain electrode; a first insulator over the first conductor; a second insulator over the second conductor; a third insulator over the first insulator and the second insulator; a fourth insulator over the third insulator; a fifth insulator that is over the oxide and placed between the first conductor and the second conductor; a sixth insulator over the fifth insulator; and a third conductor over the sixth insulator, the third conductor functioning as a gate electrode, wherein the third conductor comprises a region overlapping the oxide, wherein the fifth insulator comprises a region in contact with the oxide, the first conductor, the second conductor, the first insulator, the second insulator, the third insulator, and the fourth insulator, and wherein the fifth insulator contains nitrogen, oxygen, and silicon.
 8. The semiconductor device according to claim 7, wherein the sixth insulator contains hafnium.
 9. The semiconductor device according to claim 7, wherein a thickness of the sixth insulator is greater than or equal to 0.5 nm and less than or equal to 5.0 nm.
 10. The semiconductor device according to claim 7, wherein a thickness of the fifth insulator is greater than or equal to 0.5 nm and less than or equal to 15.0 nm.
 11. The semiconductor device according to claim 7, wherein the oxide is an oxide semiconductor containing any one or more selected from In, Ga, and Zn.
-