

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12414425
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Chu; Dong-Il et al.

Display apparatus having a substrate hole

Abstract

A display apparatus can include a substrate having a penetrating area and a separating area, the penetrating area including a substrate hole, a first buffer layer having a first-buffer lower layer, and a first-buffer upper layer, a first thin film transistor including a first semiconductor pattern, a first gate electrode, and a first source electrode and a first drain electrode, a first interlayer insulating film; a second interlayer insulating film, an opening extending through the second interlayer insulating film, the first interlayer insulating film, the first gate insulating film and the first-buffer upper layer, and a separation structure in the opening, the separation structure including a first separation layer having a same stacked structure as the first-buffer upper layer, a second separation layer having a same stacked structure as the first gate insulating film, and a third separation layer having a same stacked structure as the first gate electrode.

Inventors: Chu; Dong-Il (Gimpo-si, KR), Kim; Min-Joo (Seoul, KR), Lee; Jae-Won (Goyang-si, KR), Pak; Sang-Hoon (Seoul, KR), Won; Sang-Hyuk (Gimpo-si, KR), Youk; Seung-Hyun (Paju-si, KR), Lee; Seon-Hee (Incheon, KR)

Applicant: LG Display Co., Ltd. (Seoul, KR)

Family ID: 76547481

Assignee: LG DISPLAY CO., LTD. (Seoul, KR)

Appl. No.: 18/535829

Filed: December 11, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20240113152 A1	Apr. 04, 2024

Foreign Application Priority Data

KR	10-2019-0180056	Dec. 31, 2019
----	-----------------	---------------

Related U.S. Application Data

division parent-doc US 17136967 20201229 US 11901398 child-doc US 18535829

Publication Classification

Int. Cl.: H10H29/14 (20250101); H10D30/67 (20250101); H10H20/815 (20250101); H10H20/831 (20250101); H10H20/857 (20250101)

U.S. Cl.:

CPC H10H29/142 (20250101); H10D30/6713 (20250101); H10D30/6755 (20250101); H10H20/815 (20250101); H10H20/831 (20250101); H10H20/857 (20250101);

Field of Classification Search

CPC: H01L (27/156); H01L (29/78618); H01L (29/7869); H01L (33/12); H01L (33/38); H01L (33/62); H10H (20/815); H10H (29/142); H10H (20/857); H10H (20/831); H10K (59/124); H10K (59/873); H10K (50/84); H10K (59/12); H10K (59/00); H10K (59/1213); H10K (59/131); H10K (59/65); H10K (59/40); H10K (50/844); H10K (50/8445); H10D (30/6755); H10D (86/60); H10D (86/40); H10D (86/441); H10D (30/6713)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2017/0148856	12/2016	Choi	N/A	H10K 59/873
2017/0149014	12/2016	Choi et al.	N/A	N/A
2019/0214447	12/2018	Kim	N/A	H10K 59/1216
2020/0052054	12/2019	Park	N/A	H10K 59/00
2020/0258960	12/2019	Choi	N/A	H10K 59/121
2021/0036197	12/2020	Noh	N/A	H10H 20/853
2021/0226163	12/2020	Ji	N/A	H10K 50/844

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
106887523	12/2016	CN	N/A
107240596	12/2016	CN	N/A
10-2017-0059864	12/2016	KR	N/A
10-2017-0135587	12/2016	KR	N/A
20170135587	12/2016	KR	H01L 51/5253
10-2019-0069952	12/2018	KR	N/A
10-2019-0108212	12/2018	KR	N/A

OTHER PUBLICATIONS

KR-20170135587-A-English translation (Year: 2017). cited by examiner

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a Divisional Application of U.S. patent application Ser. No. 17/136,967 filed on Dec. 29, 2020, which claims priority to Korean Patent Application No. 10-2019-0180056 filed on Dec. 31, 2019 in the Republic of Korea, in which the entire contents of all these applications are hereby expressly incorporated by reference into the present application.

BACKGROUND

Field

(1) The present disclosure relates to a display apparatus including a substrate hole which penetrates a substrate.

Discussion of the Related Art

(2) Generally, an electric appliance such as a monitor, a television (TV), a notebook computer, or a digital camera includes a display apparatus to realize an image. For example, the display apparatus can include light emitting elements. Each of the light emitting elements can emit light displaying a specific color. For example, each of the light emitting elements can include a light emitting layer disposed between a first electrode and a second electrode.

(3) A peripheral appliance such as a camera, a speaker or a sensor can be mounted in the display apparatus. For example, the display apparatus can include a substrate hole penetrating a substrate which supports the light emitting elements. The substrate hole can be disposed between the light emitting elements. The peripheral appliance can be inserted into the substrate hole.

(4) However, in the display apparatus, external moisture can permeate through the substrate hole. The external moisture permeating through the substrate hole can move to the light emitting elements adjacent the substrate hole through the light emitting layer. Thus, in the display apparatus, the light emitting elements which are disposed adjacent the substrate hole can be damaged due to the external moisture permeating through the substrate hole.

SUMMARY OF THE INVENTION

(5) Accordingly, the present disclosure is directed to a display apparatus that substantially obviates one or more problems due to limitations and disadvantages of the related art.

(6) An object of the present disclosure is to provide a display apparatus capable of preventing damage of a light emitting element due to external moisture permeating through a substrate hole.

(7) Another object of the present disclosure is to provide a display apparatus capable of simplifying a process for blocking the external moisture.

(8) Additional advantages, objects, and features of the disclosure will be set forth in part in the description which follows and in part will become apparent to those having ordinary skill in the art upon examination of the following or can be learned from practice of the disclosure. The objectives and other advantages of the disclosure can be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

(9) To achieve these objects and other advantages and in accordance with the purpose of the disclosure, as embodied and broadly described herein, there is provided a display apparatus comprises a substrate. The substrate includes a penetrating area and a separating area. The penetrating area includes a substrate hole. The separating area surrounds the penetrating area. A first buffer layer includes a first-buffer lower layer on the substrate, and a first-buffer upper layer disposed on the first-buffer lower layer. A first thin film transistor is disposed on the first-buffer

upper layer and includes a first semiconductor pattern, a first gate electrode, a first source electrode and a first drain electrode. The first semiconductor pattern includes poly-silicon. The first gate electrode overlaps the first semiconductor pattern under a condition that a first gate insulating film is interposed between the first gate electrode and the first semiconductor pattern. The first source electrode and the first drain electrode are connected to the first semiconductor pattern. A second thin film transistor includes a second semiconductor pattern, a second gate electrode, a second source electrode and a second drain electrode. The second semiconductor pattern includes an oxide semiconductor. The second gate electrode overlaps the second semiconductor pattern under a condition that a second gate insulating film is interposed between the second gate electrode and the second semiconductor pattern. The second source electrode and the second drain electrode are connected to the second semiconductor pattern. A separation structure is disposed in the separating area of the substrate. The separation structure includes a first separation layer having the same stacked structure as the first-buffer upper layer, a second separation layer having the same stacked structure as the first gate insulating film, and a third separation layer having the same stacked structure as the first gate electrode.

(10) In another aspect of the present disclosure, there is provided a display apparatus comprising a substrate. The substrate includes a penetrating area and a separating area. The penetrating area includes a substrate hole. The separating area surrounds the penetrating area. A first buffer layer includes a first-buffer lower layer on the substrate, and a first-buffer upper layer disposed on the first-buffer lower layer. A first thin film transistor includes a first semiconductor pattern, a first gate electrode, a first source electrode and a first drain electrode. The first semiconductor pattern is disposed on the first-buffer upper layer. The first gate electrode overlaps the first semiconductor pattern under a condition that a first gate insulating film is interposed between the first gate electrode and the first semiconductor pattern. The first source electrode and the first drain electrode are connected to the first semiconductor pattern. A first interlayer insulating film is disposed on the first gate electrode. A second interlayer insulating film is disposed on the first interlayer insulating film. An opening extends through the second interlayer insulating film, the first interlayer insulating film, the first gate insulating film and the first-buffer upper layer, to expose the first-buffer lower layer disposed in the separating area. A separation structure is disposed in the opening. The separation structure includes a first separation layer having the same stacked structure as the first-buffer upper layer, a second separation layer having the same stacked structure as the first gate insulating film, and a third separation layer having the same stacked structure as the first gate electrode. The first separation layer is in contact with the first-buffer lower layer.

(11) In still another aspect of the present disclosure, there is provided a display apparatus comprising a substrate. The substrate includes a penetrating area and a separating area. The penetrating area includes a substrate hole. The separating area surrounds the penetrating area. A first buffer layer is disposed on the substrate. A first thin film transistor includes a first semiconductor pattern, a first gate electrode, a first source electrode and a first drain electrode. The first semiconductor pattern is disposed on the first buffer layer. The first gate electrode overlaps the first semiconductor pattern under a condition that a first gate insulating film is interposed between the first gate electrode and the first semiconductor pattern. The first source electrode and the first drain electrode are connected to the first semiconductor pattern. A first interlayer insulating film is disposed on the first gate electrode. A second interlayer insulating film is disposed on the first interlayer insulating film. An opening extends through the second interlayer insulating film, the first interlayer insulating film, the first gate insulating film and the first-buffer upper layer, to expose the substrate disposed in the separating area. A separation structure is disposed in the opening. The separation structure includes a first separation layer contacting the substrate, a second separation layer on the first separation layer, and a third separation layer on the second separation layer.

(12) It is to be understood that both the foregoing general description and the following detailed

description of the present disclosure are exemplary and explanatory and are intended to provide further explanation of the disclosure as claimed.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The accompanying drawings, which are included to provide a further understanding of the disclosure and are incorporated in and constitute a part of this application, illustrate embodiment(s) of the disclosure and along with the description serve to explain the principle of the disclosure. In the drawings:

- (2) FIG. 1 is a view schematically illustrating a display apparatus according to an exemplary embodiment of the present disclosure;
- (3) FIG. 2 is an enlarged view of an area around a substrate hole in the display apparatus according to the exemplary embodiment of the present disclosure;
- (4) FIG. 3 is a view illustrating a cross-section of a pixel in the display apparatus according to the exemplary embodiment of the present disclosure;
- (5) FIG. 4A is a view illustrating a cross-section of the substrate hole in the display apparatus according to the exemplary embodiment of the present disclosure
- (6) FIG. 4B is an enlarged view of an area P1 in FIG. 4A;
- (7) FIG. 5A is a view illustrating a cross-section of a substrate hole in a display apparatus according to another exemplary embodiment of the present disclosure;
- (8) FIG. 5B is an enlarged view of an area P2 in FIG. 5A,
- (9) FIG. 6 is a view illustrating a cross-section of a pixel in a display apparatus according to another exemplary embodiment of the present disclosure;
- (10) FIG. 7A is a view illustrating a cross-section of a substrate hole in the display apparatus according to another exemplary embodiment of the present disclosure;
- (11) FIG. 7B is an enlarged view of an area P3 in FIG. 7A; and
- (12) FIG. 8 is a view illustrating a cross-section of a separation structure in a display apparatus according to another exemplary embodiment of the present disclosure.

DETAILED DESCRIPTION OF THE EMBODIMENTS

(13) Details of objects and technical configurations of the present disclosure, and functions and effects thereof will be clarified through the following detailed description given with reference to the accompanying drawings illustrating embodiments of the present disclosure. Here, embodiments of the present disclosure are provided so that the present disclosure can be sufficiently thorough and complete to assist those skilled in the art in fully understanding the scope of the present disclosure. Therefore, the present disclosure can be embodied in different forms and should not be construed as limited to the embodiments set forth herein.

(14) Throughout the specification, elements designated by the same reference numerals represent the same constituent elements. In the drawings, the length and thickness of each layer or region can be exaggerated for convenience. It will be understood that the case in which a first constituent element is referred to as being “on” a second constituent element includes not only the case in which the first constituent element is disposed on the second constituent element such that the first constituent element directly contacts the second constituent element, but also the case in which a third constituent element is interposed between the first constituent element and the second constituent element.

(15) It will be understood that although the terms “first”, “second”, or the like are used herein to describe various constituent elements, these terms are only used to distinguish one constituent element from another constituent element and may not define any order. Of course, the first constituent element and the second constituent element can be optionally named in accordance with

convenience of those skilled in the art.

(16) The terminology used in the specification of the present disclosure is for the purpose of describing particular embodiments only and is not intended to limit the present disclosure. For example, a constituent element expressed in the singular form is intended to include a plurality of constituent elements, unless the context clearly indicates otherwise. It will be further understood that the terms “comprising” or “having” when used in the specification of the present disclosure, specify the presence of stated features, integers, steps, operations, elements, components or combinations thereof, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, or combinations thereof.

(17) Unless otherwise defined, all terms including technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which example embodiments belong. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and should not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

(18) FIG. 1 is a view schematically illustrating a display apparatus according to an exemplary embodiment of the present disclosure. FIG. 2 is an enlarged view of an area around a substrate hole in the display apparatus according to the exemplary embodiment of the present disclosure. FIG. 3 is a view illustrating a cross-section of a pixel in the display apparatus according to the exemplary embodiment of the present disclosure. FIG. 4A is a view illustrating a cross-section of the area around the substrate hole in the display apparatus according to the exemplary embodiment of the present disclosure. FIG. 4B is an enlarged view of an area P1 in FIG. 4A. All components of the display apparatus according to all embodiments of the present disclosure are operatively coupled and configured.

(19) Referring to FIGS. 1 to 4B, a display apparatus DP according to the exemplary embodiment of the present disclosure can include a substrate 100. The substrate 100 can include a display area in which pixels PA are disposed, and a non-display area disposed adjacent to the display area. The substrate 100 can include an insulating material. For example, the substrate 100 can include glass or plastic. The substrate 100 can have a multilayer structure. For example, the substrate 100 has a structure in which an inorganic insulating layer 102 is disposed between a first substrate layer 101 and a second substrate layer 103. The second substrate layer 103 can include the same material as the first substrate layer 101. For example, the first substrate layer 101 and the second substrate layer 103 can include plastic. The inorganic insulating layer 102 can include an insulating material. For example, the first substrate layer 101 and the second substrate layer 103 can be made of polyimide (PI), and the inorganic insulating layer 102 can include a layer made of silicon nitride (SiN.sub.x) or silicon oxide (SiO.sub.x). The inorganic insulating layer 102 can have a multilayer structure in which a layer made of silicon nitride (SiN.sub.x) and a layer made of silicon oxide (SiO.sub.x) are stacked. For example, the inorganic insulating layer 102 can include a layer made of silica or silicon dioxide (SiO.sub.2).

(20) In the display apparatus, the inorganic insulating layer 102 is formed between the first substrate layer 101 and the second substrate layer 103, which are made of polyimide (PI), such that electric charges which are charged in the first substrate layer 101 disposed at a lower side can be blocked. Further, the external moisture permeating through the first substrate layer 101 and the second substrate layer 103 which are made of polyimide (PI), can be blocked by the inorganic insulating layer 102 disposed between the first substrate layer 101 and the second substrate layer 103. Thus, the reliability of the display apparatus DP according to the exemplary embodiment of the present disclosure can be improved.

(21) The substrate 100 can include the pixels PA defined by gate lines GL and data lines DL. A light emitting element 500 can be disposed in each pixel PA. Each of the light emitting elements 500 can emit light displaying a specific color. For example, each of the light emitting elements 500

can include a first electrode **510**, a light emitting layer **520** and a second electrode **530**, which are sequentially stacked.

(22) The first electrode **510** can include a conductive material. The first electrode **510** can include a metal having relatively high reflectance. The first electrode **510** can have a multilayer structure. For example, the first electrode **510** can have a structure in which a reflective electrode made of a metal such as aluminum (Al) and silver (Ag) is disposed between transparent electrodes made of a transparent conductive material such as indium tin oxide (ITO) and indium zinc oxide (IZO).

(23) The light emitting layer **520** can generate light having luminance corresponding to a voltage difference between the first electrode **510** and the second electrode **530**. For example, the light emitting layer **520** can include an emission material layer (EML) **522** including an emission material. The emission material can include an organic material, an inorganic material or a hybrid material. For example, the display apparatus according to the exemplary embodiment of the present disclosure can be an organic light emitting display apparatus including the light emitting layer **520** made of an organic material. Alternatively, the display apparatus according to the exemplary embodiment of the present disclosure can be an inorganic light emitting display apparatus including the light emitting layer **520** made of an inorganic material.

(24) The light emitting layer **520** can have a multilayer structure in order to increase luminous efficacy. For example, the light emitting layer **520** can further include at least one first intermediate layer **521** disposed between the first electrode **510** and the emission material layer **522**, and at least one second intermediate layer **523** disposed between the emission material layer **522** and the second electrode **530**. The first intermediate layer **521** can include at least one of a hole injection layer HIL and a hole transport layer HTL. The second intermediate layer **523** can include at least one of an electron transport layer ETL and an electron injection layer EIL. However, the disclosure is not limited thereto. For example, the first intermediate layer **521** can include at least one of an electron transport layer ETL and an electron injection layer EIL, and the second intermediate layer **523** can include at least one of a hole injection layer HIL and a hole transport layer HTL.

(25) The second electrode **530** can include a conductive material. The second electrode **530** can include a material different from the first electrode **510**. For example, the second electrode **530** can be a transparent electrode made of a transparent conductive material such as ITO and IZO. Thus, in the display apparatus according to the exemplary embodiment of the present disclosure, the light generated from the light emitting layer **520** can emit outside through the second electrode **530**.

(26) A driving current corresponding to a gate signal applied by a corresponding gate line GL and a data signal applied by a corresponding data line DL can be supplied to each light emitting element **500**. For example, a pixel circuit electrically connected to the corresponding light emitting element **500** can be disposed in each pixel PA. The pixel circuit can control the operation of the corresponding light emitting element **500** according to the gate signal and the data signal. For example, the pixel circuit can include a first thin film transistor **200**, a second thin film transistor **300** and a storage capacitor **400**.

(27) The first thin film transistor **200** can include a first semiconductor pattern **210**, a first gate electrode **230**, a first source electrode **250** and a first drain electrode **260**. The second thin film transistor **300** can include a second semiconductor pattern **310**, a second gate electrode **330**, a second source electrode **350** and a second drain electrode **360**. The storage capacitor **400** can include a first storage electrode **410**, a second storage electrode **420** and a third storage electrode **430**.

(28) A first buffer layer **110** can be disposed between the substrate **100** and the pixel circuit of each pixel PA. The first buffer layer **110** can prevent pollution from the substrate **100** during a process of forming the pixel circuits. For example, the first buffer layer **110** can be formed between the substrate **100** and the first semiconductor pattern **210** of each pixel PA. The first buffer layer **110** can include an insulating material. For example, the first buffer layer **110** can include a silicon oxide (SiO.sub.x)-based material and/or a silicon nitride (SiN.sub.x)-based material. The first

buffer layer **110** can have a multilayer structure. For example, the first buffer layer **110** can include a first-buffer lower layer **111** and a first-buffer upper layer **112**.

(29) Referring to FIG. 3, the first-buffer lower layer **111** of the first buffer layer **110** can be formed on the substrate **100**. The first-buffer upper layer **112** can be formed on the first-buffer lower layer **111**. The first-buffer lower layer **111** can be formed by a multilayer structure which includes a layer made of a silicon nitride (SiN.sub.x)-based material and a layer made of a silicon oxide (SiO.sub.x)-based material. The first-buffer lower layer **111** can be formed by a multilayer structure in which a silicon oxide (SiO.sub.x) layer and a silicon nitride (SiN.sub.x) layer are alternately stacked. For example, the first-buffer lower layer **111** can be formed by a multilayer structure in which a silicon oxide (SiO.sub.x) layer and a silicon nitride (SiN.sub.x) layer are stacked, in this order.

(30) The first-buffer upper layer **112** can be formed by a single layer made of a silicon oxide (SiO.sub.x)-based material. For example, the first-buffer upper layer **112** can be formed by a single layer made of silicon dioxide (SiO.sub.2).

(31) The first semiconductor pattern **210** can be disposed on the first-buffer upper layer **112**. The first semiconductor pattern **210** can include a semiconductor material. For example, the first semiconductor pattern **210** can include poly-silicon (poly-Si) which is a poly-crystalline semiconductor material. For example, the first semiconductor pattern **210** can include low-temperature poly-silicon (LTPS).

(32) The first semiconductor pattern **210** can include a first source region **210S**, a first drain region **210D**, and a first channel region **210C**. The first channel region **210C** can be disposed between the first source region **210S** and the first drain region **210D**. The first channel region **210C** can have relatively lower conductivity than the first source region **210S** and the first drain region **210D**. For example, each of the first source region **210S** and the first drain region **210D** can have a greater conductive impurity content than the first channel region **210C**.

(33) A first gate insulating film **120** can be disposed on the first semiconductor pattern **210**. The first gate insulating film **120** can extend beyond the first semiconductor pattern **210**. The first gate insulating film **120** can include an insulating material. For example, the first gate insulating film **120** can include a silicon oxide (SiO.sub.x)-based material. The silicon oxide (SiO.sub.x)-based material can include silicon dioxide (SiO.sub.2). However, the disclosure is not limited thereto, and the first gate insulating film **120** can include a silicon nitride (SiN.sub.x)-based material. Alternatively, the first gate insulating film **120** can be formed by a multilayer structure including a silicon nitride (SiN.sub.x)-based material layer and a silicon oxide (SiO.sub.x)-based material layer.

(34) The first gate electrode **230** of the first thin film transistor **200** and the first storage electrode **410** of the storage capacitor **400** can be disposed on the first gate insulating film **120**. For example, the first gate electrode **230** can overlap the first channel region **210C** of the first semiconductor pattern **210**. The first gate electrode **230** can be insulated from the first semiconductor pattern **210** by the first gate insulating film **120**.

(35) The first storage electrode **410** and the first gate electrode **230** can include a conductive material. For example, the first gate electrode **230** can include a metal such as aluminum (Al), chromium (Cr), copper (Cu), titanium (Ti), molybdenum (Mo), a tungsten (W), or an alloy thereof. Each of the first storage electrode **410** and the first gate electrode **230** can be constituted by a single layer made of metal or an alloy material or multilayers thereof. The first storage electrode **410** and the first gate electrode **230** can be made of the same material, and can be disposed on the same layer.

(36) The first interlayer insulating film **130** can be disposed on the first storage electrode **410**, the first gate insulating film **120**, and the first gate electrode **230**. The first interlayer insulating film **130** can extend along the first gate insulating film **120**. The first interlayer insulating film **130** can include an insulating material. The first interlayer insulating film **130** can include a material

different from the first gate insulating film **120**. For example, the first gate insulating film **120** can include a silicon oxide (SiO.sub.x)-based material, and t

(37) The first interlayer insulating film **130** can include a silicon nitride (SiN.sub.x)-based material. However, the disclosure is not limited thereto, and the first interlayer insulating film **130** can be formed by a multilayer structure including a silicon nitride (SiN.sub.x)-based material layer and a silicon oxide (SiO.sub.x)-based material layer.

(38) The second storage electrode **420** and a metal pattern **450** can be formed on the first interlayer insulating film **130**. The second storage electrode **420** can overlap the first storage electrode **410** under the condition that the first interlayer insulating film **130** is interposed between the second storage electrode **420** and the first storage electrode **410**. The metal pattern **450** and the second storage electrode **420** can include a metal such as aluminum (Al), chromium (Cr), molybdenum (Mo), tungsten (W), copper (Cu), or an alloy thereof. Each of the metal pattern **450** and the second storage electrode **420** can be constituted by a single layer made of metal or an alloy material, or multiple layers thereof. The metal pattern **450** and the second storage electrode **420** can include the same material as the first storage electrode **410**.

(39) As illustrated in FIG. 3, the metal pattern **450** and the second storage electrode **420** can be formed to be spaced apart from each other when viewed in a cross-sectional view. However, the disclosure is not limited thereto, and the metal pattern **450** and the second storage electrode **420** can be formed to have an integrated structure in which the metal pattern **450** and the second storage electrode **420** are connected.

(40) A second buffer layer **140** can be formed on the first interlayer insulating film **130**, the metal pattern **450** and the second storage electrode **420**. The second buffer layer **140** can be formed by a multilayer structure constituted by a silicon nitride (SiN.sub.x)-based material and a silicon oxide (SiO.sub.x)-based material. The second buffer layer **140** can be formed by a multilayer structure in which a silicon oxide (SiO.sub.x) layer and a silicon nitride (SiN.sub.x) layer are alternately stacked. The uppermost layer of the second buffer layer **140** contacting the second semiconductor pattern **310** of the second thin film transistor **300** can be a silicon oxide (SiO.sub.x) layer. However, the disclosure is not limited thereto, and the second buffer layer **140** can be formed by a single layer made of silicon nitride (SiN.sub.x) or silicon oxide (SiO.sub.x).

(41) Referring to FIG. 3, the second semiconductor pattern **310** of the second thin film transistor **300** can be formed on the second buffer layer **140**. The second semiconductor pattern **310** can overlap the metal pattern **450**. The second semiconductor pattern **310** can include a material different from the first semiconductor pattern **210**. The second semiconductor pattern **310** can include an oxide semiconductor. For example, the second semiconductor pattern **310** can include at least one of an IZO (InZnO)-based oxide semiconductor material, an IGO (InGaO)-based oxide semiconductor material, an ITO (InSnO)-based oxide semiconductor material, an IGZO (InGaZnO)-based oxide semiconductor material, an IGZTO (InGaZnSnO)-based oxide semiconductor material, an ITZO (InSnZnO)-based oxide semiconductor material, an IGTO (InGaSnO)-based oxide semiconductor material, a GO (GaO)-based oxide semiconductor material, a GZTO (GaZnSnO)-based oxide semiconductor material, and a GZO (GaZnO)-based oxide semiconductor material. However, the disclosure is not limited thereto, and the second semiconductor pattern **310** can be made of another oxide semiconductor material known in the art. The second semiconductor pattern **310** can include a second source region **310S**, a second drain region **310D**, and a second channel region **310C**. The second channel region **310C** can be disposed between the second source region **310S** and the second drain region **310D**. Resistance of the second source region **310S** and resistance of the second drain region **310D** can be lower than resistance of the second channel region **310C**. For example, each of the second source region **310S** and the second drain region **310D** can be a conductorized region. The second channel region **310C** can be a region which is not conductorized. The second channel region **310C** of the second semiconductor pattern **310** can overlap with the metal pattern **450**.

(42) The second gate insulating film **150** can be disposed on the second buffer layer **140** and the second semiconductor pattern **310**. The second gate insulating film **150** can include an insulating material. For example, the second gate insulating film **150** can include at least one of a silicon oxide (SiO.sub.x) material and a silicon nitride (SiN.sub.x) material. The second gate insulating film **150** can have a single-layer structure or a multilayer structure.

(43) The second gate electrode **330** of the second thin film transistor **300** can be disposed on the second gate insulating film **150**. The second gate electrode **330** can overlap with the second channel region **310C** of the second semiconductor pattern **310** under the condition that the second gate insulating film **150** is interposed between the second gate electrode **330** and the second channel region **310C**. The second gate electrode **330** can include a conductive material. For example, the second gate electrode **330** can include a metal such as aluminum (Al), chromium (Cr), copper (Cu), titanium (Ti), molybdenum (Mo), tungsten (W), or an alloy thereof. The second gate electrode **330** can be formed by a single layer or multiple layers. For example, the second gate electrode **330** can be formed by multiple layers including a metal layer of molybdenum (Mo) and a metal layer of titanium (Ti). When viewed in a cross-sectional view, the width of the metal layer of titanium (Ti) can be greater than the width of the metal layer of molybdenum (Mo).

(44) The second interlayer insulating film **160** can be disposed on the second gate insulating film **150** and the second gate electrode **330**. The second interlayer insulating film **160** can include an insulating material. The second interlayer insulating film **160** can be constituted by a single layer made of a silicon oxide (SiO.sub.x) material or a silicon nitride (SiN.sub.x) material, or multiple layers thereof. For example, the second interlayer insulating film **160** can be formed by multiple layers including a silicon oxide (SiO.sub.x) layer and a silicon nitride (SiN.sub.x) layer.

(45) A contact hole can be formed to expose the first semiconductor pattern **210** of the first thin film transistor **200** by etching the second interlayer insulating film **160**, the second gate insulating film **150**, the second buffer layer **140**, the first interlayer insulating film **130**, and the first gate insulating film **120**. For example, the first source region **210S** and the first drain region **210D** of the first semiconductor pattern **210** can be exposed by the contact hole, respectively. A contact hole can be formed to expose the second semiconductor pattern **310** of the second thin film transistor **300** by etching the second interlayer insulating film **160** and the second gate insulating film **150**.

Therefore, the second source region **310S** and the second drain region **310D** of the second semiconductor pattern **310** can be exposed by the contact hole, respectively.

(46) A contact hole can be formed to expose the second storage electrode **420** of the storage capacitor **400** by etching the second interlayer insulating film **160**, the second gate insulating film **150**, and the second buffer layer **140**. Thus, the second storage electrode **420** of the storage capacitor **400** can be exposed by the contact hole.

(47) The second source electrode **350** and the second drain electrode **360** of the second thin film transistor **300**, the first source electrode **250** and the first drain electrode **260** of the first thin film transistor **200**, and the third storage electrode **430** of the storage capacitor **400** can be disposed on the second interlayer insulating film **160**.

(48) The second source electrode **350** and the second drain electrode **360** of the second thin film transistor **300** can be connected to the second source region **310S** and the second drain region **310D** of the second semiconductor pattern **310** through the contact hole which is formed in the second interlayer insulating film **160**, the second gate insulating film **150**, the second buffer layer **140**, the first interlayer insulating film **130** and the first gate insulating film **120**, respectively.

(49) The first source electrode **250** and the first drain electrode **260** of the first thin film transistor **200** can be connected to the first source region **210S** and the first drain region **210D** of the first semiconductor pattern **210** through the contact hole formed in the second interlayer insulating film **160** and the second gate insulating film **150**, respectively.

(50) The third storage electrode **430** of the storage capacitor **400** can be connected to the second storage electrode **420** through the contact hole formed in the second interlayer insulating film **160**,

the second gate insulating film **150** and the second buffer layer **140**.

(51) The second source electrode **350**, the second drain electrode **360**, the first source electrode **250**, the first drain electrode **260**, and the third storage electrode **430** can be made of the same material, and can be disposed on the same layer. The second source electrode **350**, the second drain electrode **360**, the first source electrode **250**, the first drain electrode **260**, and the third storage electrode **430** can be formed by a single layer or multiple layers made of at least one of molybdenum (Mo), copper (Cu), titanium (Ti), aluminum (Al), chromium (Cr), gold (Au), nickel (Ni), and neodymium (Nd), and an alloy thereof. For example, each of the second source electrode **350**, the second drain electrode **360**, the first source electrode **250**, the first drain electrode **260**, and the third storage electrode **430** can be formed to have a triple-layer structure. For example, each of the second source electrode **350**, the second drain electrode **360**, the first source electrode **250**, the first drain electrode **260**, and the third storage electrode **430** can have a structure in which an intermediate layer including a metal layer of titanium (Ti) is interposed between the lower layer and the upper layer which are a metal layer of aluminum (Al).

(52) The third storage electrode **430** can be electrically connected to the second drain electrode **360** of the second thin film transistor **300**. For example, the third storage electrode **430** can be formed to have a structure integrated with the second drain electrode **360** of the second thin film transistor **300**, such that the third storage electrode **430** and the second drain electrode **360** are connected.

(53) A first passivation layer **171** of a passivation layer **170** can be formed on the second source electrode **350**, the second drain electrode **360**, the first source electrode **250**, the first drain electrode **260**, and the third storage electrode **430**.

(54) A contact hole exposing the first drain electrode **260** of the first thin film transistor **200** can be formed in the first passivation layer **171**. However, the disclosure is not limited thereto, and a contact hole exposing the first source electrode **250** of the first thin film transistor **200** can be formed in the first passivation layer **171**. A contact hole exposing the second drain electrode **360** or the second source electrode **350** of the second thin film transistor **300** can be formed in the first passivation layer **171**. The first passivation layer **171** can be made of an inorganic material or an organic material. For example, the first passivation layer **171** can include an inorganic material, such as a silicon oxide (SiO₂)-based material and a silicon nitride (SiN_x)-based material. For example, the first passivation layer **171** can be made of an organic material, such as acryl resin, epoxy resin, phenolic resin, polyamide resin and polyimide resin.

(55) An auxiliary electrode **600** can be formed on the first passivation layer **171**. The auxiliary electrode **600** can be connected to the first drain electrode **260** of the first thin film transistor **200** exposed by the contact hole in the first passivation layer **171**. However, the disclosure is not limited thereto, and the auxiliary electrode **600** can be connected to the second drain electrode **360** or the second source electrode **350** of the second thin film transistor **300** by the contact hole in the first passivation layer **171**. The auxiliary electrode **600** can be formed by a single layer or multiple layers made of at least one of molybdenum (Mo), copper (Cu), titanium (Ti), aluminum (Al), chromium (Cr), gold (Au), nickel (Ni), and neodymium (Nd), and an alloy thereof. The auxiliary electrode **600** can include the same material as the second drain electrode **360**.

(56) A second passivation layer **172** can be formed on the first passivation layer **171** and the auxiliary electrode **600**. A contact hole exposing the auxiliary electrode **600** can be formed in the second passivation layer **172**. The second passivation layer **172** can remove a thickness difference due to the pixel circuit of each pixel PA. For example, an upper surface of the second passivation layer **172** toward the light emitting element **500** of each pixel PA can be a flat surface. The second passivation layer **172** can include an organic insulating material. For example, the second passivation layer **172** can be made of an organic material, such as acryl resin, epoxy resin, phenolic resin, polyamide resin, and polyimide resin. The second passivation layer **172** can include a material different from the first passivation layer **171**.

(57) The light emitting element **500** of each pixel PA can be electrically connected to the first thin

film transistor of the corresponding pixel PA. For example, the first electrode of each pixel PA can be connected to the auxiliary electrode **600** by penetrating the second passivation layer **172** and, the auxiliary electrode **600** can be connected to the first drain electrode **260** of the first thin film transistor **200** by penetrating the first passivation layer **171**. Thus, the first electrode **510** of each pixel PA can be electrically connected to the first thin film transistor **200**. The first thin film transistor **200** connected to the first electrode **510** of the light emitting element **500** can be a driving thin film transistor configured to supply driving current to the light emitting element **500**. However, the disclosure is not limited thereto, and the first electrode **510** of the light emitting element **500** can be connected to the second thin film transistor **300**. In this case, the second thin film transistor **300** connected to the first electrode **510** can become a driving thin film transistor configured to supply driving current to the light emitting element **500**.

(58) The first electrode **510** can be formed to have a multilayer structure which includes a transparent conductive film and an opaque conductive film having high reflection efficiency. The transparent conductive film can be made of a material having a relatively larger work function value such as indium tin oxide (ITO) and indium zinc oxide (IZO). The opaque conductive film can be formed by a single layer or multiple layers including aluminum (Al), silver (Ag), copper (Cu), lead (Pb), molybdenum (Mo), titanium (Ti) or an alloy thereof. For example, the first electrode **510** can have a structure in which a transparent conductive film, an opaque conductive film and a transparent conductive film are stacked, in this order. However, the disclosure is not limited thereto, and the first electrode **510** can have a structure in which a transparent conductive film and an opaque conductive film can be sequentially formed.

(59) The display apparatus according to the exemplary embodiment of the present disclosure can be a top emission display apparatus in which the first electrode **510** is an anode. However, the disclosure is not limited thereto. For example, the display apparatus according to the exemplary embodiment of the present disclosure can be a bottom emission display apparatus in which the first electrode **510** on the passivation layer **170** is a cathode.

(60) The light emitting element **500** of each pixel PA can be independently operated. For example, the first electrode **510** of each pixel PA can be insulated from the first electrode **510** of adjacent pixel PA. And edge of each first electrode **510** can be covered by a bank layer **180**. The bank layer **180** can be disposed on the second passivation layer **172**. The light emitting layer **520** and the second electrode **530** of each pixel PA can be stacked on the first electrode **510** exposed by the bank layer **180**. The bank layer **180** can include an insulating material. For example, the bank layer **180** can include an organic insulating material. The bank layer **180** can include a material different from the second passivation layer **172**. The bank layer **180** can define an emission area of the display apparatus. For example, the bank layer **180** can be referred to as a “pixel definition film”. A spacer **190** can be disposed on the bank layer **180**.

(61) At least a portion of the light emitting layer **520** of each pixel PA can extend onto the bank layer **180**. For example, the first intermediate layer **521** and the second intermediate layer **523** of each pixel PA can be connected to the first intermediate layer **521** and the second intermediate layer **523** of adjacent pixel PA. The emission material layer **522** of each pixel PA can be spaced apart from the light emitting material layer **522** of adjacent pixel PA. The second electrode **530** of each pixel PA can extend onto the bank layer **180**. For example, the second electrode **530** of each pixel PA can be connected to the second electrode **530** of adjacent pixel PA.

(62) An encapsulating element to prevent permeation of moisture can be disposed on the second electrode **530**. The encapsulating element can include a first encapsulation layer, a second encapsulation layer and a third encapsulation layer. The second encapsulation layer can include a material different from the first encapsulation layer and the third encapsulation layer. For example, each of the first and third encapsulation layers can be an inorganic insulating film made of an inorganic insulating material, and the second encapsulation layer can be an organic insulating film made of an organic insulating material. The first encapsulation layer of the encapsulating element

can be disposed on the second electrode **530**. The second encapsulation layer can be disposed on the first encapsulation layer. The third encapsulation layer can be disposed on the second encapsulation layer.

(63) The first and third encapsulation layers of the encapsulating element can be made of an inorganic material such as silicon nitride (SiN.sub.x) and silicon oxide (SiO.sub.x). The second encapsulation layer of the encapsulating element can be made of an organic material such as acryl resin, epoxy resin, phenolic resin, polyamide resin, and polyimide resin.

(64) In the display apparatus according to the exemplary embodiment of the present disclosure, the first thin film transistor **200** can function as a driving transistor. Thus, the first electrode **510** of the light emitting element **500** can be connected to the first thin film transistor **200**, but the disclosure is not limited thereto. For example, the first electrode **510** of the light emitting element **500** can be connected to the second thin film transistor **300**, and the second thin film transistor **300** can function as a driving transistor.

(65) Referring to FIG. **4A**, a substrate hole CH can be formed in the display area of the substrate **100**. The substrate hole CH can penetrate the substrate **100**. The substrate hole CH can be disposed among the pixels PA in the display area. Thus, the substrate hole CH can be formed in the display area. For example, the substrate hole CH can be formed among the light emitting elements **500**. The substrate **100** can include a hole peripheral area HA including an area in which the substrate hole CH is formed. The light emitting elements **500** can be disposed outside the hole peripheral area HA. The gate lines GL and the data lines DL can bypass the substrate hole CH along an edge of the substrate hole CH in the hole peripheral area HA.

(66) The hole peripheral area HA can include a penetrating area CA in which the substrate hole CH is formed, and a separating area SA surrounding the penetrating area CA. For example, the separating area SA can be disposed between the penetrating area CA and the pixels PA.

(67) At least one separation structure **700** can be disposed in the separating area SA. The separation structure **700** can include an undercut structure.

(68) Referring to FIG. **4B**, the separation structure **700** can include a first separation layer **711**, a second separation layer **712**, and a third separation layer **713**. The first separation layer **711** can be formed on the first-buffer lower layer **111** of the first buffer layer **110**. For example, the first separation layer **711** can be made of the same material as the first-buffer upper layer **112** of the first buffer layer **110**, and can be formed on the same layer as the first-buffer upper layer **112**. The first separation layer **711** can have the same stacked structure as the first-buffer upper layer **112**. A lower surface of the first separation layer **711** can contact an upper surface of the first-buffer lower layer **111**. The thickness of the first separation layer **711** can be the same as the thickness of the first-buffer upper layer **112**.

(69) The second separation layer **712** can be disposed on the first separation layer **711**. The second separation layer **712** can be made of the same material as the first gate insulating film **120**, and can be formed on the same layer as the first gate insulating film **120**. The thickness of the second separation layer **712** can be the same as the thickness of the first gate insulating film **120**. The second separation layer **712** can have the same stacked structure as the first gate insulating film **120**. The third separation layer **713** can be disposed on the second separation layer **712**. The second separation layer **712** can be disposed between the third separation layer **713** and the first separation layer **711**. The third separation layer **713** can be made of the same material as the first gate electrode **230** of the first thin film transistor **200**, and can be formed on the same layer as the first gate electrode **230**. The third separation layer **713** can have the same stacked structure as the first gate electrode **230**. For example, each of the first and second separation layers **711** and **712** can include an insulating material layer, and the third separation layer **713** can include a metal material layer.

(70) The third separation layer **713** can be larger width than each of the first and second separation layers **711** and **712**. For example, a lower surface of the third separation layer **713** can have a

greater length than an upper surface of the second separation layer **712**. An end of the third separation layer **713** can protrude from a side surface of the second separation layer **712**, such that both ends of the third separation layer **713** may not overlap with the second separation layer **712**. Thus, the separation structure **700** can have an undercut structure. In the display apparatus according to the exemplary embodiment of the present disclosure, the second electrode **530** and the light emitting layer **520** deposited in the separating area SA can be completely separated by the separation structure **700**. For example, as illustrated in FIG. **4B**, the first and second intermediate layers **521** and **523** of the light emitting layer **520** and the second electrode **530** can be separated by the separation structure **700**. Therefore, in the display apparatus according to the exemplary embodiment of the present disclosure, permeation of the external moisture through the light emitting layer **520** can be blocked by the separation structure **700**. The second electrode **530** can be separated by the undercut structure of each separation structure **700**.

(71) The separation structure **700** can be formed using a process of forming a thin film transistor and an insulating material layer. For example, the formation of the separation structures **700** can include a step of forming the first buffer layer **110** and the first gate insulating film **120** on the separating area SA, a step of forming the third separation layer **713** made of the same metal material as the first gate electrode **230**, a step of depositing the first interlayer insulating film **130**, the second buffer layer **140**, the second gate insulating film **150**, and the second interlayer insulating film **160** on the third separation layer **713** and the first gate insulating film **120**, and a step of forming the first separation layer **711** and the second separation layer **712** using an etching process. For example, the etching process can include a process of patterning the first interlayer insulating film **130**, the second buffer layer **140**, the second gate insulating film **150**, and the second interlayer insulating film **160** which are stacked on the third separation layer **713** to expose the third separation layer **713**, and a process of removing a portion of the first-buffer upper layer **112** and a portion of the first gate insulating film **120** which are exposed by the third separation layer **713**. A portion of the first-buffer upper layer **112** overlapping with the third separation layer **713** can become the first separation layer **711**. A portion of the first gate insulating film **120** overlapping with the third separation layer **713** can become the second separation layer **712**.

(72) The first separation layer **711** can be formed by an etching process of the first-buffer upper layer **112** on the separating area SA. The first separation layer **711** can have the same stacked structure as the first-buffer upper layer **112** on the separating area SA, and can be made of the same material as the first-buffer upper layer **112**. For example, the first separation layer **711** can include a silicon oxide (SiO₂)-based material. The second separation layer **712** can be formed by an etching process of the first gate insulating film **120** on the separating area SA. The second separation layer **712** can have the same stacked structure as the first gate insulating film **120**, and can be made of the same material as the first gate insulating film **120**. Thus, in the display apparatus according to the exemplary embodiment of the present disclosure, any layer can be not added for the formation of separation structures **700**, and the degradation of the process efficiency for forming the display apparatus can be minimized.

(73) The second interlayer insulating film **160**, the second gate insulating film **150**, the second buffer layer **140**, the first interlayer insulating film **130**, the first gate insulating film **120** and the first-buffer upper layer **112** of the first buffer layer **110** can include an opening OP exposing the first-buffer lower layer **111** on the separating area SA by an etching process. The separation structure **700** can be disposed on the first-buffer lower layer **111** exposed by the opening OP. The third separation layer **713**, which is the uppermost layer of the separation structure **700**, can be made of a metal material, and the first and second separation layers **711** and **712** disposed between the uppermost layer of the separation structure **700**, for example, the third separation layer **713**, and the first-buffer lower layer **111** can be made of an insulating material.

(74) The light emitting layer **520** and the second electrode **530** can be disposed on the third separation layer **713** of the separation structure **700** which is the uppermost layer. For example, the

first and second intermediate layers **521** and **523** of the light emitting layer **520** and the second electrode **530** of the light emitting element **500** can be disposed on the third separation layer **713**. The first intermediate layer **521** can contact an upper surface of the third separation layer **713**. (75) The light emitting layer **520** and the second electrode **530** on the first-buffer lower layer **111** exposed by the opening OP can be spaced apart from the separation structure **700**). As illustrated in FIG. **4B**, the first and second intermediate layers **521** and **523** of the light emitting layer **520** and the second electrode **530** of the light emitting element **500**, which are disposed on the first-buffer lower layer **111** exposed by the opening OP, can be disposed to be spaced apart from the first separation layer **711** of the separation structure **700**. The first intermediate layer **521**, the second intermediate layer **523** and the second electrode **530** can be disposed to face both side surfaces of the first separation layer **711**. The first intermediate layer **521**, the second intermediate layer **523** and the second electrode **530** can be disposed to be spaced apart from the both side surfaces of the first separation layer **711**. The first intermediate layer **521** of the light emitting layer **520** on the first-buffer lower layer **111** exposed by the opening OP can contact the upper surface of the first-buffer lower layer **111**. The first intermediate layer **521** of the light emitting layer **520** can be disposed on the second interlayer insulating film **160** in the separating area SA. The first intermediate layer **521** in the separating area SA can contact the upper surface of the second interlayer insulating film **160**.

(76) The hole peripheral area HA can include a barrier area which is disposed outside the separating area SA. The separating area SA can be disposed between the penetrating area CA and the barrier area. At least one dam can be disposed in the barrier area.

(77) Accordingly, in the display apparatus according to the exemplary embodiment of the present disclosure, the separating area SA can be disposed between the penetrating area CA in which the substrate hole CH is formed, and the pixels PA, at least one separation structure **700** can be disposed in the separating area SA, and each separation structure **700** can include at least one undercut structure. The distance from the lower surface of the third separation layer **713** to the upper surface of the first-buffer lower layer **111** can be greater than the sum of thicknesses of the light emitting layer **520** and the second electrode **530** which are disposed in each pixel PA. For example, the sum of thicknesses of the first and second separation layers **711** and **712** can be greater than the sum of thicknesses of the first and second intermediate layers **521** and **523**, and the second electrode **530**. Thus, in the display apparatus according to the exemplary embodiment of the present disclosure, the light emitting layer **520** can be surely separated by the separation structure **700**. For example, in the display apparatus according to the exemplary embodiment of the present disclosure, the damage of the light emitting element **500** due to the external moisture permeating through the substrate hole CH can be effectively prevented. And, the display apparatus according to the exemplary embodiment of the present disclosure can form the separation structure **700** using a process of forming the pixel circuit and the light emitting element **500** of each pixel PA. Therefore, in the display apparatus according to the exemplary embodiment of the present disclosure, the degradation of the process efficiency due to the formation process for the separation structure **700** can be prevented.

(78) FIG. **5A** is a view illustrating a cross-section of a substrate hole in a display apparatus according to another exemplary embodiment of the present disclosure. FIG. **5B** is an enlarged view of an area P2 in FIG. **5A**.

(79) The following description will be given with reference to FIGS. **3**, **4A** and **4B**, and an overlapping description will be omitted or briefly given. For example, a substrate **100**, a first buffer layer **110**, a first gate insulating film **120**, a first interlayer insulating film **130**, a second buffer layer **140**, a second gate insulating film **150**, a second interlayer insulating film **160**, a passivation layer **170**, a bank layer **180**, a spacer **190**, a light emitting element **500**, an auxiliary electrode **600**, a storage capacitor **400**, a substrate hole CH, a first thin film transistor **200**, and a second thin film transistor **300** in FIGS. **5A** and **5B** are identical to those of FIGS. **3**, **4A** and **4B**. An overlapping

description of the configurations of FIGS. 5A and 5B substantially identical to those of FIGS. 3, 4A and 4B will be omitted or briefly given.

(80) As illustrated in FIG. 5B, in the display apparatus according to another exemplary embodiment of the present disclosure, the separation structure **700** can further include a fourth separation layer **714**. The separation structure **700** can include a first separation layer **711**, a second separation layer **712**, a third separation layer **713**, and the fourth separation layer **714**. The fourth separation layer **714** can be made of the same material as the first-buffer lower layer **111** of the first buffer layer **110**, and can be disposed on the same layer as the first-buffer lower layer **111**. The fourth separation layer **714** can have the same stacked structure as the first-buffer lower layer **111**, and can have the same thickness as the first-buffer lower layer **111**. Accordingly, the fourth separation layer **714** can be formed by a multilayer structure in which a silicon nitride (SiN.sub.x)-based material and a silicon oxide (SiO.sub.x)-based material are alternately formed. The fourth separation layer **714** can be disposed between the first separation layer **711** and the substrate **100**. Each of the widths of the first separation layer **711**, the second separation layer **712** and the fourth separation layer **714** can be smaller than the width of the third separation layer **713**.

(81) In the display apparatus according to another exemplary embodiment of the present disclosure, the second electrode **530** and the light emitting layer **520** deposited in the separating area SA can be completely separated by the separation structure **700**. For example, as illustrated in FIG. 5B, the second electrode **530**, the first and second intermediate layers **521** and **523** of the light emitting layer **520** can be separated by the separation structure **700**. Accordingly, in the display apparatus according to another exemplary embodiment of the present disclosure, penetration of external moisture through the light emitting layer **520** can be prevented by the separation structure **700**. The second electrode **530**, the first and second intermediate layers **521** and **523** of the light emitting layer **520** can be separated by the undercut structure of each separation structure **700**.

(82) The second interlayer insulating film **160**, the second gate insulating film **150**, the second buffer layer **140**, the first interlayer insulating film **130**, the first gate insulating film **120** and the first buffer layer **110** disposed in the separating area SA can include an opening OP formed through an etching process to expose the substrate **100**. The separation structure **700** can be disposed on the substrate **100** exposed through the opening OP. The third separation layer **713**, which is the uppermost layer of the separation structure **700**, can be made of a metal material, whereas the first, second and fourth separation layers **711**, **712** and **714** disposed between the uppermost layer of the separation structure **700**, for example, the third separation layer **713**, and the substrate **100** can be made of an insulating material.

(83) The light emitting layer **520** and the second electrode **530** can be disposed on the third separation layer **713** of the separation structure **700** which is the uppermost layer. For example, the first and second intermediate layers **521** and **523** of the light emitting layer **520** and the second electrode **530** of the light emitting element **500** can be disposed on the third separation layer **713**. The first intermediate layer **521** can contact the upper surface of the third separation layer **713**.

(84) The light emitting layer **520** and the second electrode **530** can be disposed on the substrate **100** exposed through the opening OP, and can be spaced apart from the separation structure **700**. As illustrated in FIG. 4B, the first and second intermediate layers **521** and **523** of the light emitting layer **520** and the second electrode **530** of the light emitting element **500**, which are disposed on the substrate **100** exposed through the opening OP, can be disposed to be spaced apart from the fourth separation layer **714** of the separation structure **700**. The first intermediate layer **521**, the second intermediate layer **523** and the second electrode **530** can be disposed to face opposite side surfaces of the fourth separation layer **714**. In addition, the first intermediate layer **521**, the second intermediate layer **523** and the second electrode **530** can be disposed to be spaced apart from opposite side surfaces of the first separation layer **711**. Furthermore, the first intermediate layer **521** of the light emitting layer **520** disposed on the substrate **100** exposed through the opening OP can contact the upper surface of the substrate **100**. The first intermediate layer **521** of the light emitting

layer **520** can be disposed on the second interlayer insulating film **160** disposed in the separating area SA. In addition, the first intermediate layer **521** disposed in the separating area SA can contact the upper surface of the second interlayer insulating film **160**.

(85) As a result, in the display apparatus according to another exemplary embodiment of the present disclosure, at least one separation structure **700** can be disposed in the separating area SA disposed between the penetrating area CA formed with the substrate hole CH and the pixels PA, and each separation structure **700** can include at least one undercut structure. In addition, the distance from the lower surface of the third separation layer **713** to the upper surface of the substrate **100** can be greater than the sum of thicknesses of the light emitting layer **520** and the second electrode **530** disposed in each pixel PA. For example, the sum of thicknesses of the first, second and fourth separation layers **711**, **712** and **714** can be greater than the sum of thicknesses of the first and second intermediate layers **521** and **523**, and the second electrode **530**. Accordingly, in the display apparatus according to another exemplary embodiment of the present disclosure, the light emitting layer **520** can be surely separated by the separation structure **700**. For example, in the display apparatus according to another exemplary embodiment of the present disclosure, it can be possible to effectively prevent damage to the light emitting element **500** caused by external moisture penetrating through the substrate hole CH. In addition, in the display apparatus according to another exemplary embodiment of the present disclosure, it can be possible to form the separation structure **700** using a formation process for the pixel circuit and the light emitting element **500** of each pixel PA. Thus, in the display apparatus according to another exemplary embodiment of the present disclosure, degradation in process efficiency caused by the formation process for the separation structure **700** can be avoided.

(86) FIG. **6** is a view illustrating a cross-section of a pixel in a display apparatus according to another exemplary embodiment of the present disclosure. FIG. **7A** is a view illustrating a cross-section of a substrate hole in the display apparatus according to another exemplary embodiment of the present disclosure. FIG. **7B** is an enlarged view of an area P3 in FIG. **7A**.

(87) The following description will be given with reference to FIGS. **3**, **4A** and **4B**, and an overlapping description will be omitted or briefly given. For example, a substrate **100**, a first buffer layer **110**, a first gate insulating film **120**, a first interlayer insulating film **130**, a second interlayer insulating film **160**, a passivation layer **170**, a bank layer **180**, a spacer **190**, a light emitting element **500**, an auxiliary electrode **600**, a substrate hole CH, and a separation structure **700** in FIGS. **6**, **7A** and **7B** are identical to those of FIGS. **3**, **4A** and **4B**. An overlapping description of configurations of FIGS. **6**, **7A** and **7B** substantially identical to those of FIGS. **3**, **4A** and **4B** will be omitted or briefly given.

(88) Referring to FIG. **6**, the display apparatus according to another exemplary embodiment of the present disclosure can include the substrate **100**, the first buffer layer **110**, the first gate insulating film **120**, the first interlayer insulating film **130**, the second interlayer insulating film **160**, the passivation layer **170**, the bank layer **180**, the spacer **190**, the light emitting element **500**, the auxiliary electrode **600**, a storage capacitor **400**, a first thin film transistor **200**, the substrate hole CH, and the separation structure **700**.

(89) The substrate **100** can include pixels PA defined by gate lines GL and data lines DL. The light emitting element **500** can be disposed at each pixel PA. In each pixel PA, a pixel circuit, which is electrically connected to the corresponding light emitting element **500**, can be disposed. The pixel circuit of each pixel PA can control operation of the corresponding light emitting element **500** in accordance with a gate signal and a data signal. For example, the pixel circuit can include the first thin film transistor **200** and the storage capacitor **400**.

(90) Meanwhile, the first thin film transistor **200** can include a first semiconductor pattern **210**, a first gate electrode **230**, a first source electrode **250**, and a first drain electrode **260**. In addition, the storage capacitor **400** can include a first storage electrode **410**, a second storage electrode **420**, and a third storage electrode **430**. The first semiconductor pattern **210** can be disposed on the first

buffer layer **110**. The first semiconductor pattern **210** can include a semiconductor material. For example, the first semiconductor pattern **210** can include polysilicon (poly-Si) which is a polycrystalline semiconductor material. For example, the first semiconductor pattern **210** can include low-temperature polysilicon (LTPS).

(91) The first gate insulating film **120** can be disposed on the first semiconductor pattern **210**. The first gate electrode **230** of the first thin film transistor **200** and the first storage electrode **410** of the storage capacitor **400** can be disposed on the first gate insulating film **120**. The first storage electrode **410** and the first gate electrode **230** can be made of the same material, and can be disposed on the same layer.

(92) The first interlayer insulating film **130** can be disposed on the first storage electrode **410**, the first gate insulating film **120**, and the first gate electrode **230**. The second storage electrode **420** can be formed on the first interlayer insulating film **130**.

(93) The second interlayer insulating film **160** can be formed on the first interlayer insulating film **130** and the second storage electrode **420**.

(94) Contact holes can be formed to expose the first semiconductor pattern **210** of the first thin film transistor **200** by etching the second interlayer insulating film **160**, the first interlayer insulating film **130**, and the first gate insulating film **120**. Accordingly, contact holes can be formed to expose the first source region **210S** and the first drain region **210D** in the first semiconductor pattern **210**, respectively.

(95) In addition, a contact hole can be formed to expose the second storage electrode **420** of the storage capacitor **400** by etching the second interlayer insulating film **160**. Accordingly, a contact hole can be formed to expose the second storage electrode **420** of the storage capacitor **400**.

(96) On the second interlayer insulating film **160**, the first source electrode **250** and the first drain electrode **260** in the first thin film transistor **200** and the third storage electrode **430** of the storage capacitor **400** can be disposed.

(97) The first source electrode **250** and the first drain electrode **260** in the first thin film transistor **200** can be connected to the first source region **210S** and the first drain region **210D** in the first semiconductor pattern **210** via the contact holes formed through the second interlayer insulating film **160**, the first interlayer insulating film **130** and the first gate insulating film **120**, respectively.

(98) The third storage electrode **430** of the storage capacitor **400** can be connected to the second storage electrode **420** via the contact hole formed through the second interlayer insulating film **160**.

(99) The first source electrode **250**, the first drain electrode **260** and the third storage electrode **430** can be made of the same material, and can be disposed on the same layer.

(100) A first passivation layer **171** of the passivation layer **170** can be formed on the second interlayer insulating film **160**, the first source electrode **250**, the first drain electrode **260**, and the third storage electrode **430**. A contact hole can be formed through the first passivation layer **171** in order to expose the first drain electrode **260** of the first thin film transistor **200**.

(101) An auxiliary electrode **600** can be formed on the first passivation layer **171**. The auxiliary electrode **600** can be connected to the first drain electrode **260** of the first thin film transistor **200** exposed through the contact hole of the first passivation layer **171**. A second passivation layer **172** can be formed on the first passivation layer **171** and the auxiliary electrode **600**. A contact hole can be formed through the second passivation layer **172** in order to expose the auxiliary electrode **600**. The second passivation layer **172** can eliminate a step formed due to the pixel circuit of each pixel PA. For example, the upper surface of the second passivation layer **172** directed to the light emitting element **500** of each pixel PA can be a flat surface.

(102) The light emitting element **500** of each pixel PA can be electrically connected to the first thin film transistor of the pixel PA.

(103) Referring to FIG. 7A, the substrate hole CH can be formed in the display area of the substrate **100**. The substrate hole CH can extend through the substrate **100**. The substrate hole CH can be disposed between pixels PA. Accordingly, the substrate hole CH can be formed in the display area.

For example, the substrate hole CH can be formed between the light emitting elements **500** of the pixels PA. The substrate **100** can include a hole peripheral area HA including an area in which the substrate hole CH is formed. The light emitting elements **500** can be disposed outside the hole peripheral area HA. The gate lines GL and the data lines DL in the hole peripheral area HA can bypass the substrate hole CH along an edge of the substrate hole CH.

(104) The hole peripheral area HA can include a penetrating area CA in which the substrate hole CH is formed, and a separating area SA surrounding the penetrating area CA. For example, the separating area SA can be disposed between the penetrating area CA and the pixels PA.

(105) At least one separation structure **700** can be disposed in the separating area SA. The separation structure **700** can include an undercut structure.

(106) Referring to FIG. 7B, the separation structure **700** can include a first separation layer **711**, a second separation layer **712**, and a third separation layer **713**. The first separation layer **711** can be formed on the first-buffer lower layer **111** of the first buffer layer **110**. In addition, the first separation layer **711** can be made of the same material as the first-buffer upper layer **112** of the first buffer layer **110**, and can be formed on the same layer as the first-buffer upper layer **112**.

Furthermore, the first separation layer **711** can have the same stacked structure as the first-buffer upper layer **112**. The lower surface of the first separation layer **711** can contact the upper surface of the first-buffer lower layer **111**. The thickness of the first separation layer **711** can be equal to the thickness of the first-buffer upper layer **112**.

(107) In addition, the second separation layer **712** can be disposed on the first separation layer **711**. The second separation layer **712** can be made of the same material as the first gate insulating film **120**, and can be formed on the same layer as the first gate insulating film **120**. Furthermore, the thickness of the second separation layer **712** can be equal to the thickness of the first gate insulating film **120**. In addition, the second separation layer **712** can have the same stacked structure as the first gate insulating film **120**. Meanwhile, the third separation layer **713** can be disposed on the second separation layer **712**. The second separation layer **712** can be disposed between the third separation layer **713** and the first separation layer **711**. In addition, the third separation layer **713** can be made of the same material as the first gate electrode **230** of the first thin film transistor **200**, and can be formed on the same layer as the first gate electrode **230**. Furthermore, the third separation layer **713** can have the same stacked structure as the first gate electrode **230**. As such, each of the first and second separation layers **711** and **712** can be constituted by an insulating material layer, whereas the third separation layer **713** can be constituted by a metal material layer.

(108) The width of the third separation layer **713** can be greater than each of those of the first and second separation layers **711** and **712**. For example, the lower surface of the third separation layer **713** can have a greater length than the upper surface of the second separation layer **712**. Opposite ends of the third separation layer **713** may not overlap with the second separation layer **712**, and can protrude from opposite side surfaces of the second separation layer **712**, respectively. As such, the separation structure **700** can have an undercut structure. In the display apparatus according to another exemplary embodiment of the present disclosure, the second electrode **530** and the light emitting layer **520** deposited in the separating area SA can be completely separated by the separation structure **700**. For example, as illustrated in FIG. 7B, the second electrode **530** and the first and second intermediate layers **521** and **523** of the light emitting layer **520** can be separated by the separation structure **700**. Accordingly, in the display apparatus according to the exemplary embodiment of the present disclosure, penetration of external moisture through the light emitting layer **520** can be prevented by the separation structure **700**. The second electrode **530** can be separated by the undercut structure of each separation structure **700**.

(109) The separation structure **700** can be formed using a process for forming a thin film transistor and an insulating material layer. For example, for formation of separation structures **700**, the first buffer layer **110** and the first gate insulating film **120** can be formed in the separating area SA. In addition, the third separation layer **713**, which is made of the same metal material as the first gate

electrode **230**, can be formed. Subsequently, the first interlayer insulating film **130**, and the second interlayer insulating film **160** are deposited on the third separation layer **713** and the first gate insulating film **120**. Thereafter, the first separation layer **711** and the second separation layer **712** can be formed using an etching process. For example, through an etching process, the first interlayer insulating film **130** and the second interlayer insulating film **160** deposited on the third separation layer **713** can be patterned to expose the third separation layer **713**. Thereafter, the first-buffer upper layer **112** and the first gate insulating film **120** disposed in an area defined beneath the third separation layer **713** while overlapping with the third separation layer **713** can be patterned and, as such, can be formed into the first separation layer **711** and the second separation layer **712**. The first-buffer upper layer **112** can be patterned and, as such, can be formed into the first separation layer **711**, whereas the first gate insulating film **120** can be patterned and, as such, can be formed into the second separation layer **712**.

(110) The first separation layer **711** can be formed through an etching process for the first-buffer upper layer **112** formed in the separating area SA. The first separation layer **711** can have the same stacked structure as the first-buffer upper layer **112** formed in the separating area SA, and can be made of the same material as the first-buffer upper layer **112**. For example, the first separation layer **711** can include a silicon oxide (SiO₂)-based material. The second separation layer **712** can be formed through an etching process for the first gate insulating film **120** formed in the separating area SA. As such, the second separation layer **712** can have the same stacked structure as the first gate insulating film **120**, and can be made of the same material as the first gate insulating film **120**. Accordingly, in the display apparatus according to another exemplary embodiment of the present disclosure, no separate layer is added for formation of separation structures **700** and, as such, degradation in the process efficiency for formation of the display apparatus can be minimized.

(111) The second interlayer insulating film **160**, the first interlayer insulating film **130**, the first gate insulating film **120** and the first-buffer upper layer **112** of the first buffer layer **110** disposed in the separating area SA can include an opening OP formed through an etching process to expose the first-buffer lower layer **111**. The separation structure **700** can be disposed on the first-buffer lower layer **111** exposed through the opening OP. The third separation layer **713**, which is the uppermost layer of the separation structure **700**, can be made of a metal material, whereas the first and second separation layers **711** and **712** disposed between the uppermost layer of the separation structure **700**, for example, the third separation layer **713**, and the first-buffer lower layer **111** can be made of an insulating material.

(112) The light emitting layer **520** and the second electrode **530** can be disposed on the third separation layer **713** of the separation structure **700** which is the uppermost layer. For example, the first and second intermediate layers **521** and **523** of the light emitting layer **520** and the second electrode **530** of the light emitting element **500** can be disposed on the third separation layer **713**. The first intermediate layer **521** can contact the upper surface of the third separation layer **713**.

(113) The light emitting layer **520** and the second electrode **530** can be disposed on the first-buffer lower layer **111** exposed through the opening OP, and can be spaced apart from the separation structure **700**. As illustrated in FIG. 7B, the first and second intermediate layers **521** and **523** of the light emitting layer **520** and the second electrode **530** of the light emitting element **500**, which are disposed on the first-buffer lower layer **111** exposed through the opening OP, can be disposed to be spaced apart from the first separation layer **711** of the separation structure **700**. The first intermediate layer **521**, the second intermediate layer **523** and the second electrode **530** can be disposed to face opposite side surfaces of the first separation layer **711**. In addition, the first intermediate layer **521**, the second intermediate layer **523** and the second electrode **530** can be disposed to be spaced apart from the opposite side surfaces of the first separation layer **711**. Furthermore, the first intermediate layer **521** of the light emitting layer **520** disposed on the first-buffer lower layer **111** exposed through the opening OP can contact the upper surface of the first-buffer lower layer **111**. The first intermediate layer **521** of the light emitting layer **520** can be

disposed on the second interlayer insulating film **160** disposed in the separating area SA. In addition, the first intermediate layer **521** disposed in the separating area SA can contact the upper surface of the second interlayer insulating film **160**.

(114) The hole peripheral area HA can further include a barrier area disposed outside the separating area SA. The separating area SA can be disposed between the penetrating area CA and the barrier area BA. At least one dam can be disposed in the barrier area BA.

(115) As a result, in the display apparatus according to another exemplary embodiment of the present disclosure, at least one separation structure **700** can be disposed in the separating area SA disposed between the penetrating area CA formed with the substrate hole CH and the pixels PA, and each separation structure **700** can include at least one undercut structure. In addition, the distance from the lower surface of the third separation layer **713** to the upper surface of the first-buffer lower layer **111** can be greater than the sum of thicknesses of the light emitting layer **520** and the second electrode **530** disposed in each pixel PA. For example, the sum of thicknesses of the first and second separation layers **711** and **712** can be greater than the sum of thicknesses of the first and second intermediate layers **521** and **523**, and the second electrode **530**. Accordingly, in the display apparatus according to another exemplary embodiment of the present disclosure, the light emitting layer **520** can be surely separated by the separation structure **700**. For example, in the display apparatus according to another exemplary embodiment of the present disclosure, it can be possible to effectively prevent damage to the light emitting element **500** caused by external moisture penetrating through the substrate hole CH. In addition, in the display apparatus according to another exemplary embodiment of the present disclosure, it can be possible to form the separation structure **700** using a formation process for the pixel circuit and the light emitting element **500** of each pixel PA. Thus, in the display apparatus according to another exemplary embodiment of the present disclosure, degradation in process efficiency caused by the formation process for the separation structure **700** can be avoided.

(116) FIG. **8** is a view illustrating a cross-section of a separation structure in a display apparatus according to another exemplary embodiment of the present disclosure. The following description will be given with reference to FIGS. **6** and **7B**, and an overlapping description will be omitted or briefly given. For example, a substrate **100**, a first buffer layer **110**, a first gate insulating film **120**, a first interlayer insulating film **130**, a second interlayer insulating film **160**, a passivation layer **170**, a bank layer **180**, a spacer **190**, a light emitting element **500**, an auxiliary electrode **600**, a storage capacitor **400**, a substrate hole CH, and a first thin film transistor **200** in FIG. **8** are identical to those of FIGS. **6** and **7B**. An overlapping description of configurations of FIG. **8** substantially identical to those of FIGS. **6** and **7B** will be omitted or briefly given.

(117) As illustrated in FIG. **8**, in the display apparatus according to another exemplary embodiment of the present disclosure, the separation structure **700** can further include a fourth separation layer **714**. The separation structure **700** can include a first separation layer **711**, a second separation layer **712**, a third separation layer **713**, and the fourth separation layer **714**. The fourth separation layer **714** can be made of the same material as the first-buffer lower layer **111** of the first buffer layer **110**, and can be disposed on the same layer as the first-buffer lower layer **111**. The fourth separation layer **714** can have the same stacked structure as the first-buffer lower layer **111**, and can have the same thickness as the first-buffer lower layer **111**. Accordingly, the fourth separation layer **714** can be formed by a multilayer structure in which a silicon oxide (SiO₂)-based material and a silicon nitride (SiN)-based material are alternately formed. The fourth separation layer **714** can be disposed between the first separation layer **711** and the substrate **110**. Each of the widths of the first separation layer **711**, the second separation layer **712** and the fourth separation layer **714** can be smaller than the width of the third separation layer **713**.

(118) In the display apparatus according to another exemplary embodiment of the present disclosure, the second electrode **530** and the light emitting layer **520** deposited in the separating area SA can be completely separated by the separation structure **700**. For example, as illustrated in

FIG. 8, the second electrode **530**, the first and second intermediate layers **521** and **523** of the light emitting layer **520** can be separated by the separation structure **700**. Accordingly, in the display apparatus according to another exemplary embodiment of the present disclosure, penetration of external moisture through the light emitting layer **520** can be prevented by the separation structure **700**. The second electrode **530**, the first and second intermediate layers **521** and **523** of the light emitting layer **520** can be separated by the undercut structure of each separation structure **700**.

(119) The second interlayer insulating film **160**, the first interlayer insulating film **130**, the first gate insulating film **120** and the first buffer layer **110** disposed in the separating area SA can include an opening OP formed through an etching process to expose the substrate **100**. The separation structure **700** can be disposed on the substrate **100** exposed through the opening OP. The third separation layer **713**, which is the uppermost layer of the separation structure **700**, can be made of a metal material, whereas the first, second and fourth separation layers **711**, **712** and **714** disposed between the uppermost layer of the separation structure **700**, for example, the third separation layer **713**, and the substrate **100** can be made of an insulating material.

(120) The light emitting layer **520** and the second electrode **530** can be disposed on the third separation layer **713** of the separation structure **700** which is the uppermost layer. For example, the first and second intermediate layers **521** and **523** of the light emitting layer **520** and the second electrode **530** of the light emitting element **500** can be disposed on the third separation layer **713**. The first intermediate layer **521** can contact the upper surface of the third separation layer **713**.

(121) The light emitting layer **520** and the second electrode **530** can be disposed on the substrate **100** exposed through the opening OP, and can be spaced apart from the separation structure **700**. As illustrated in FIG. 8, the first and second intermediate layers **521** and **523** of the light emitting layer **520** and the second electrode **530** of the light emitting element **500**, which are disposed on the substrate **100** exposed through the opening OP, can be disposed to be spaced apart from the fourth separation layer **714** of the separation structure **700**. The first intermediate layer **521**, the second intermediate layer **523** and the second electrode **530** can be disposed to face opposite side surfaces of the fourth separation layer **714**. In addition, the first intermediate layer **521**, the second intermediate layer **523** and the second electrode **530** can be disposed to be spaced apart from opposite side surfaces of the first separation layer **711**. Furthermore, the first intermediate layer **521** of the light emitting layer **520** disposed on the substrate **100** exposed through the opening OP can contact the upper surface of the substrate **100**. The first intermediate layer **521** of the light emitting layer **520** can be disposed on the second interlayer insulating film **160** disposed in the separating area SA. In addition, the first intermediate layer **521** disposed in the separating area SA can contact the upper surface of the second interlayer insulating film **160**.

(122) As a result, in the display apparatus according to another exemplary embodiment of the present disclosure, at least one separation structure **700** can be disposed in the separating area SA disposed between the penetrating area CA formed with the substrate hole CH and the pixels PA, and each separation structure **700** can include at least one undercut structure. In addition, the distance from the lower surface of the third separation layer **713** to the upper surface of the substrate **100** can be greater than the sum of thicknesses of the light emitting layer **520** and the second electrode **530** disposed in each pixel PA. For example, the sum of thicknesses of the first and second separation layers **711** and **712**, and the fourth separation layer **714** can be greater than the sum of thicknesses of the first and second intermediate layers **521** and **523**, and the second electrode **530**. Accordingly, in the display apparatus according to another exemplary embodiment of the present disclosure, the light emitting layer **520** can be surely separated by the separation structure **700**. For example, in the display apparatus according to another exemplary embodiment of the present disclosure, it can be possible to effectively prevent damage to the light emitting element **500** caused by external moisture penetrating through the substrate hole CH. In addition, in the display apparatus according to another exemplary embodiment of the present disclosure, it can be possible to form the separation structure **700** using a formation process for the pixel circuit and the

light emitting element **500** of each pixel PA. Thus, in the display apparatus according to another exemplary embodiment of the present disclosure, degradation in process efficiency caused by the formation process for the separation structure **700** can be avoided.

(123) A display apparatus according to one exemplary embodiment of the present disclosure can include a substrate including a penetrating area including a substrate hole, and a separating area surrounding the penetrating area, a first buffer layer including a first-buffer lower layer disposed on the substrate, and a first-buffer upper layer disposed on the first-buffer lower layer, a first thin film transistor including a first semiconductor pattern disposed on the first-buffer upper layer while including polysilicon, a first gate electrode overlapping with the first semiconductor pattern under a condition that a first gate insulating film is interposed between the first gate electrode and the first semiconductor pattern, and a first source electrode and a first drain electrode, which are connected to the first semiconductor pattern, a second thin film transistor including a second semiconductor pattern including an oxide semiconductor, a second gate electrode overlapping with the second semiconductor pattern under a condition that a second gate insulating film is interposed between the second gate electrode and the second semiconductor pattern, and a second source electrode and a second drain electrode, which are connected to the second semiconductor pattern, and a separation structure disposed in the separating area of the substrate, the separation structure including a first separation layer having the same stacked structure as the first-buffer upper layer, a second separation layer having the same stacked structure as the first gate insulating film, and a third separation layer having the same stacked structure as the first gate electrode.

(124) In accordance with an embodiment of the present disclosure, the third separation layer can include the same metal material as the first gate electrode, the first separation layer can include the same insulating material as the first-buffer upper layer, and the second separation layer can include the same insulating material as the first gate insulating film.

(125) In accordance with an embodiment of the present disclosure, the second separation layer can be disposed between the third separation layer and the first separation layer.

(126) In accordance with an embodiment of the present disclosure, the display apparatus can further include a light emitting element connected to the first thin film transistor. In this case, the light emitting element can include a first electrode, a light emitting layer disposed on the first electrode, and a second electrode disposed on the light emitting layer.

(127) In accordance with an embodiment of the present disclosure, the light emitting layer can include a first intermediate layer, a light emitting material layer disposed on the first intermediate layer, and a second intermediate layer disposed on the light emitting material layer.

(128) In accordance with an embodiment of the present disclosure, the first intermediate layer, the second intermediate layer, and the second electrode can be disposed on the third separation layer of the separation structure, and the first intermediate layer can contact an upper surface of the third separation layer.

(129) In accordance with an embodiment of the present disclosure, the third separation layer can have a greater width than each of the first separation layer and the second separation layer.

(130) In accordance with an embodiment of the present disclosure, the third separation layer can be an uppermost layer of the separation structure.

(131) In accordance with an embodiment of the present disclosure, the separation structure can further include a fourth separation layer disposed between the first separation layer and the substrate. The fourth separation layer can include the same stacked structure and the same insulating material as the first-buffer lower layer.

(132) A display apparatus according to another exemplary embodiment of the present disclosure can include a substrate including a penetrating area including a substrate hole, and a separating area surrounding the penetrating area, a first buffer layer including a first-buffer lower layer disposed on the substrate, and a first-buffer upper layer disposed on the first-buffer lower layer, a first thin film transistor including a first semiconductor pattern disposed on the first-buffer upper layer, a first

gate electrode overlapping with the first semiconductor pattern under a condition that a first gate insulating film is interposed between the first gate electrode and the first semiconductor pattern, and a first source electrode and a first drain electrode, which are connected to the first semiconductor pattern, a first interlayer insulating film disposed on the first gate electrode, a second interlayer insulating film disposed on the first interlayer insulating film, an opening extending through the second interlayer insulating film, the first interlayer insulating film, the first gate insulating film and the first-buffer upper layer, to expose the first-buffer lower layer disposed in the separating area, and a separation structure disposed in the opening, the separation structure including a first separation layer contacting the first-buffer lower layer while having the same stacked structure as the first-buffer upper layer, a second separation layer having the same stacked structure as the first gate insulating film, and a third separation layer having the same stacked structure as the first gate electrode.

(133) In accordance with an embodiment of the present disclosure, the third separation layer can have a greater width than each of the first separation layer and the second separation layer.

(134) In accordance with an embodiment of the present disclosure, the third separation layer is an uppermost layer of the separation structure.

(135) In accordance with an embodiment of the present disclosure, the display apparatus can further include a light emitting element connected to the first thin film transistor. In this case, the light emitting element can include a first electrode, a light emitting layer disposed on the first electrode, and a second electrode disposed on the light emitting layer.

(136) In accordance with an embodiment of the present disclosure, the light emitting layer can include a first intermediate layer, a light emitting material layer disposed on the first intermediate layer, and a second intermediate layer disposed on the light emitting material layer.

(137) In accordance with an embodiment of the present disclosure, the first intermediate layer, the second intermediate layer, and the second electrode can be disposed on the third separation layer of the separation structure, and the first intermediate layer can contact an upper surface of the third separation layer.

(138) A display apparatus according to another exemplary embodiment of the present disclosure can include a substrate including a penetrating area including a substrate hole, and a separating area surrounding the penetrating area, a first buffer layer disposed on the substrate, a first thin film transistor including a first semiconductor pattern disposed on the first buffer layer, a first gate electrode overlapping with the first semiconductor pattern under a condition that a first gate insulating film is interposed between the first gate electrode and the first semiconductor pattern, and a first source electrode and a first drain electrode, which are connected to the first semiconductor pattern, a first interlayer insulating film disposed on the first gate electrode, a second interlayer insulating film disposed on the first interlayer insulating film, an opening extending through the second interlayer insulating film, the first interlayer insulating film, the first gate insulating film and the first buffer layer, to expose the substrate disposed in the separating area, and a separation structure disposed in the opening, the separation structure including a first separation layer contacting the substrate, a second separation layer disposed on the first separation layer, and a third separation layer disposed on the second separation layer.

(139) In accordance with an embodiment of the present disclosure, the first separation layer can include the same material as the first buffer layer while having the same stacked structure as the first buffer layer. The second separation layer can include the same material as the first gate insulating film while having the same stacked structure as the first gate insulating film. The third separation layer can include the same material as the first gate electrode while having the same stacked structure as the first gate electrode.

(140) In accordance with an embodiment of the present disclosure, the third separation layer can have a greater width than each of the first separation layer and the second separation layer.

(141) In accordance with an embodiment of the present disclosure, the third separation layer can be

an uppermost layer of the separation structure.

(142) In accordance with an embodiment of the present disclosure, the display apparatus can further include a light emitting element connected to the first thin film transistor. In this case, the light emitting element can include a first electrode, a light emitting layer disposed on the first electrode, and a second electrode disposed on the light emitting layer.

(143) In accordance with an embodiment of the present disclosure, the light emitting layer can include a first intermediate layer, a light emitting material layer disposed on the first intermediate layer, and a second intermediate layer disposed on the light emitting material layer.

(144) In accordance with an embodiment of the present disclosure, the first intermediate layer, the second intermediate layer, and the second electrode can be disposed on the third separation layer of the separation structure, and the first intermediate layer can contact an upper surface of the third separation layer.

(145) In the display apparatus according to each exemplary embodiment of the present disclosure, at least one separation structure can be disposed between the substrate hole and the light emitting elements. Each light emitting element can include a light emitting layer disposed between the first electrode and the second electrode. Each separation structure can include at least one undercut structure. Each undercut structure can have a greater depth and a greater length than the thickness of the light emitting layer. Accordingly, in the display apparatus according to each exemplary embodiment of the present disclosure, a migration path of external moisture penetrating through the substrate hole can be blocked by the separation structure. Thus, in the display apparatus according to each exemplary embodiment of the present disclosure, lifespan and reliability of the light emitting elements can be enhanced.

(146) Those skilled in the art to which the present disclosure pertains can appreciate that various modifications and applications in the foregoing description can be possible without changing essential characteristics of the embodiments. Therefore, the above-described embodiments should be understood as exemplary rather than limiting in all aspects. In addition, the scope of the present disclosure should also be defined by the claims below rather than the above detailed description. All modifications or alterations as would be derived from the equivalent concept intended to be included within the scope of the present disclosure should also be interpreted as falling within the scope of the present disclosure.

Claims

1. A display apparatus comprising: a substrate comprising a penetrating area and a separating area surrounding the penetrating area, the penetrating area comprising a substrate hole; a first buffer layer comprising a first-buffer lower layer disposed on the substrate, and a first-buffer upper layer disposed on the first-buffer lower layer; a first thin film transistor comprising a first semiconductor pattern disposed on the first-buffer upper layer, a first gate electrode overlapping with the first semiconductor pattern under a condition that a first gate insulating film is interposed between the first gate electrode and the first semiconductor pattern, and a first source electrode and a first drain electrode, which are connected to the first semiconductor pattern; a first interlayer insulating film disposed on the first gate electrode; a second interlayer insulating film disposed on the first interlayer insulating film; an opening extending through the second interlayer insulating film, the first interlayer insulating film, the first gate insulating film and the first-buffer upper layer, to expose the first-buffer lower layer disposed in the separating area; a separation structure disposed in the opening, the separation structure comprising a first separation layer contacting the first-buffer lower layer while having a same stacked structure as the first-buffer upper layer, a second separation layer having a same stacked structure as the first gate insulating film, and a third separation layer having a same stacked structure as the first gate electrode; and a light emitting element connected to the first thin film transistor, wherein the third separation layer which is an

uppermost layer of the separation structure, has a greater width than each of the first separation layer and the second separation layer, and wherein a side of the third separation layer has a different shape from a side of the first separation layer and a side of the second separation layer, wherein the light emitting element comprises a first electrode, a light emitting layer disposed on the first electrode, and a second electrode disposed on the light emitting layer, wherein the light-emitting layer includes a first intermediate layer, a light emitting material layer disposed on the first intermediate layer, and a second intermediate layer disposed on the light emitting material layer, and wherein at least one of the first intermediate layer and the second intermediate layer extends to the substrate hole, such that at least one of the first intermediate layer and the second intermediate layer is separated by the separation structure on the separating area.

2. The display apparatus according to claim 1, wherein the substrate hole has a structure in which a plurality of layers is stacked.

3. The display apparatus according to claim 1, wherein the first intermediate layer, the second intermediate layer, and the second electrode are disposed on the third separation layer of the separation structure, and wherein the first intermediate layer contacts an upper surface of the third separation layer.

4. The display apparatus according to claim 1, further comprising: a first planarization layer covering the first source electrode and the first drain electrode of the first thin film transistor; a connection electrode on the first planarization layer, the connection electrode electrically connected to the first thin film transistor; and a second planarization layer on the first planarization layer, the second planarization layer covering the connection electrode, wherein the light emitting element is disposed on the second planarization layer, and wherein the first electrode of the light emitting element is electrically connected to the connection electrode.

5. The display apparatus according to claim 4, wherein the first planarization layer is disposed on the second interlayer insulating film.

6. The display apparatus according to claim 1, wherein the separation structure includes at least one undercut structure.

7. The display apparatus according to claim 1, wherein a distance from a lower surface of the third separation layer to an upper surface of the first-buffer lower layer is greater than a sum of thicknesses of the light emitting layer and the second electrode.

8. The display apparatus according to claim 1, further comprising a second thin film transistor comprising a second semiconductor pattern including a material different from the first semiconductor pattern, a second gate electrode overlapping with the second semiconductor pattern under a condition that a second gate insulating film is interposed between the second gate electrode and the second semiconductor pattern, and a second source electrode and a second drain electrode, which are connected to the second semiconductor pattern.

9. The display apparatus according to claim 8, wherein the first semiconductor layer includes a low-temperature poly-silicon (LTPS), and the second semiconductor layer includes an oxide semiconductor.

10. The display apparatus according to claim 8, further comprising a metal pattern disposed between the substrate and the second semiconductor layer, wherein the second semiconductor layer is disposed on a layer different from the first semiconductor layer.

11. The display apparatus according to claim 10, wherein the metal pattern is disposed on a same layer as the first gate electrode.

12. A display apparatus comprising: a substrate comprising a penetrating area and a separating area surrounding the penetrating area, the penetrating area comprising a substrate hole; a first buffer layer disposed on the substrate; a first thin film transistor comprising a first semiconductor pattern disposed on the first buffer layer, a first gate electrode overlapping with the first semiconductor pattern under a condition that a first gate insulating film is interposed between the first gate electrode and the first semiconductor pattern, and a first source electrode and a first drain electrode,

which are connected to the first semiconductor pattern; a first interlayer insulating film disposed on the first gate electrode; a second interlayer insulating film disposed on the first interlayer insulating film; an opening extending through the second interlayer insulating film, the first interlayer insulating film, the first gate insulating film and the first buffer layer, to expose the substrate disposed in the separating area; a separation structure disposed in the opening, the separation structure comprising a first separation layer contacting the substrate, a second separation layer disposed on the first separation layer, and a third separation layer disposed on the second separation layer; and a light emitting element connected to the first thin film transistor, wherein the third separation layer which is an uppermost layer of the separation structure, has a greater width than each of the first separation layer and the second separation layer, and wherein a side of the third separation layer has a different shape from a side of the first separation layer and a side of the second separation layer, wherein the light emitting element comprises a first electrode, a light emitting layer disposed on the first electrode, and a second electrode disposed on the light emitting layer, wherein the light-emitting layer includes a first intermediate layer, a light emitting material layer disposed on the first intermediate layer, and a second intermediate layer disposed on the light emitting material layer, and wherein at least one of the first intermediate layer and the second intermediate layer extends to the substrate hole, such that at least one of the first intermediate layer and the second intermediate layer is separated by the separation structure on the separating area.

13. The display apparatus according to claim 12, wherein: the first separation layer comprises a same material as the first buffer layer while having a same stacked structure as the first buffer layer; the second separation layer comprises a same material as the first gate insulating film while having a same stacked structure as the first gate insulating film; and the third separation layer comprises a same material as the first gate electrode while having a same stacked structure as the first gate electrode.

14. The display apparatus according to claim 12, further comprising: a storage capacitor including a first storage electrode and a second storage electrode on the first storage electrode, wherein the first storage electrode is disposed on a same layer as the first gate electrode of the first thin film transistor.

15. The display apparatus according to claim 14, wherein the first storage electrode includes a same material as the first gate electrode.

16. The display apparatus according to claim 14, further comprising: a second thin film transistor comprising a second semiconductor pattern disposed on a layer different from the first semiconductor pattern, a second gate electrode overlapping with the second semiconductor pattern under a condition that a second gate insulating film is interposed between the second gate electrode and the second semiconductor pattern, and a second source electrode and a second drain electrode, which are connected to the second semiconductor pattern; and a metal pattern disposed between the substrate and the second semiconductor layer, wherein the second storage electrode is disposed on a same layer as the metal pattern.

17. The display apparatus according to claim 16, wherein the second storage electrode includes a same material as the metal pattern.

18. The display apparatus according to claim 16, wherein the metal pattern is disposed between the first interlayer insulating film and the second interlayer insulating film.

19. The display apparatus according to claim 18, wherein the first source electrode and the first drain electrode of the first thin film transistor are disposed on the second interlayer insulating film, wherein the storage capacitor includes a third storage electrode connected to the second storage electrode, and wherein the third storage electrode is disposed on a same layer as the first source electrode and the first drain electrode.
