

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12389758
Kind Code	B2
Date of Patent	August 12, 2025
Inventor(s)	Ichikawa; Tomoyoshi et al.

Display device, method for manufacturing display device, and electronic apparatus with interlayer insulation film

Abstract

Provided is a display device in which more than one pixel is arranged in a two-dimensional matrix on a circuit board, the pixel including a light emission unit including a first electrode, an organic layer, and a second electrode that are stacked, in which the first electrode is disposed for each light emission unit, and a partition is formed between the first electrode and an adjacent first electrode, the organic layer and the second electrode are stacked on an entire surface including the first electrode and the partition, the first electrode is formed on an interlayer insulation film, and a reflection film is formed below the first electrode, the reflection film including a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film.

Inventors:	Ichikawa; Tomoyoshi (Kanagawa, JP), Aoyagi; Kenichi (Kanagawa, JP), Sakairi; Takashi (Kanagawa, JP)
Applicant:	Sony Semiconductor Solutions Corporation (Kanagawa, JP)
Family ID:	68468269
Assignee:	Sony Semiconductor Solutions Corporation (Kanagawa, JP)
Appl. No.:	17/052994
Filed (or PCT Filed):	April 23, 2019
PCT No.:	PCT/JP2019/017184
PCT Pub. No.:	WO2019/216198
PCT Pub. Date:	November 14, 2019

Prior Publication Data

Document Identifier	Publication Date
----------------------------	-------------------------

Foreign Application Priority Data

JP 2018-091993 May. 11, 2018

Publication Classification

Int. Cl.: H10K59/124 (20230101); H10K50/13 (20230101); H10K50/852 (20230101); H10K59/12 (20230101); H10K59/30 (20230101); H10K59/38 (20230101); H10K59/80 (20230101); H10K71/00 (20230101); H10K102/00 (20230101)

U.S. Cl.:

CPC H10K59/124 (20230201); H10K50/852 (20230201); H10K59/30 (20230201); H10K59/80518 (20230201); H10K59/878 (20230201); H10K71/00 (20230201); H10K50/131 (20230201); H10K59/1201 (20230201); H10K59/38 (20230201); H10K59/876 (20230201); H10K2102/351 (20230201)

Field of Classification Search

CPC: H10K (59/124); H10K (59/30); H10K (59/1201); H10K (59/38); H10K (71/00); H10K (50/852); H10K (50/131); H10K (2102/351); H10K (59/878); H10K (59/80518); H10K (59/876)

USPC: 257/40; 257/59

References Cited**U.S. PATENT DOCUMENTS**

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2005/0082532	12/2004	Murakami	438/151	H10K 59/124
2006/0286889	12/2005	Nishi	445/24	H10K 50/814
2011/0042696	12/2010	Smith	257/88	H10K 50/826
2011/0317429	12/2010	Aiba	427/508	H10K 50/852
2012/0018749	12/2011	Lee	257/89	H10K 50/852
2013/0193416	12/2012	Shin	257/40	H10K 50/858
2014/0167604	12/2013	Iwata	313/504	H10K 59/38
2014/0231790	12/2013	Fujino	257/89	H10K 50/865
2014/0285542	12/2013	Izumi	345/694	G09G 3/3233
2015/0187858	12/2014	Wang	257/40	H10K 59/352
2015/0228930	12/2014	Murata	N/A	N/A
2016/0064421	12/2015	Oh	257/43	H01L 27/1218
2016/0133681	12/2015	Nam	257/40	H10K 59/1216
2016/0266436	12/2015	Jiao	N/A	H10K 59/38
2017/0373280	12/2016	Lee	N/A	H10K 50/80
2018/0151628	12/2017	Park	N/A	H10K 50/818

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
101013745	12/2006	CN	N/A
103227272	12/2012	CN	N/A
103928495	12/2013	CN	N/A
105742512	12/2015	CN	N/A
107852788	12/2017	CN	N/A
2004-259607	12/2003	JP	N/A
2006-278257	12/2005	JP	N/A
2007004997	12/2006	JP	N/A
2008-135373	12/2007	JP	N/A
2015062194	12/2014	JP	N/A
10-2009-0062194	12/2008	KR	N/A
10-2009-0132356	12/2008	KR	N/A
10-2016-0039105	12/2015	KR	N/A

OTHER PUBLICATIONS

International Search Report, International Application No. PCT/JP2019/017184, dated Jul. 5, 2019. cited by applicant

Primary Examiner: Jones; Eric W

Attorney, Agent or Firm: Michael Best & Friedrich LLP

Background/Summary

TECHNICAL FIELD

(1) The present disclosure relates to a display device, a method for manufacturing a display device, and an electronic apparatus.

BACKGROUND ART

(2) In recent years, an organic electroluminescence (EL) display device employing EL based on an organic material has been attracting attention as an alternative display device to liquid crystal display devices. In addition, organic EL display devices are being applied not only to direct-view displays such as monitors but also to micro-displays in which a pixel pitch as fine as several microns is required.

(3) One method for achieving color display on an organic EL display device includes forming organic EL material layers, for each pixel, using a mask for light emission of a plurality of colors including, for example, red light emission, green light emission, and blue light emission. This method is often used for a direct-view organic EL display device. Furthermore, in addition to the aforementioned method, there is a method that includes forming an organic EL material layer for white light emission for all the pixels in common and disposing a color filter for each pixel. As the pixel pitch becomes finer, it is more difficult to form an organic EL material layer for each pixel using a mask, in terms of precision of alignment and the like. Therefore, for an organic EL display device having a pixel pitch as fine as several microns, a preferred method may be forming an organic EL material layer for white light emission for all the pixels in common, combined with using color filters.

(4) However, the method involving combination of an organic EL material layer for white light emission with a color filter suffers from reduced luminous efficacy because the white light is color-

separated by the color filter. For this reason, there is known a technology for achieving improvement in luminous efficacy and color reproducibility by employing a resonator structure for enhancing the light having a particular wavelength by a resonance effect (see Patent Document 1, for example).

CITATION LIST

Patent Document

(5) Patent Document 1: Japanese Patent Application Laid-Open No. 2006-278257

SUMMARY OF THE INVENTION

Problems to be Solved by the Invention

(6) In order to enhance the light having the target wavelength by the resonance effect, it is necessary to set the optical path length of the resonator structure with high precision. In addition, even in a case of taking light having a wide wavelength range, variations in color or the like will occur due to variations in a positional relationship between the organic layer and the reflection film. Therefore, there has been a need for a display device having a structure in which the positional relationship between the organic layer and the reflection film can be set with high precision and for a method for manufacturing such a display device.

(7) Therefore, an object of the present disclosure is to provide a display device having a structure in which the positional relationship between the organic layer and the reflection film can be set with high precision, an electronic apparatus equipped with the display device, and a method for manufacturing the display device.

Solutions to Problems

(8) For achieving the above-described object, a display device according to the present disclosure is a display device in which more than one pixel is arranged in a two-dimensional matrix on a circuit board, the pixel including a light emission unit including a first electrode, an organic layer, and a second electrode that are stacked, in which the first electrode is disposed for each light emission unit, and a partition is formed between the first electrode and an adjacent first electrode, the organic layer and the second electrode are stacked on an entire surface including the first electrode and the partition, the first electrode is formed on an interlayer insulation film, and a reflection film is formed below the first electrode, the reflection film including a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film.

(9) For achieving the above-described object, a method for manufacturing a display device according to the present disclosure is a method for manufacturing the display device in which more than one pixel is arranged in a two-dimensional matrix on a circuit board, the pixel including a light emission unit including a first electrode, an organic layer, and a second electrode that are stacked, the method including steps of: forming, on a substrate, an interlayer insulation film in which layers of different types of insulation materials are stacked to be in contact with each other; forming an opening in a region of the interlayer insulation film, the region corresponding to the first electrode, in such a way that a plane flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film is exposed to a bottom; embedding a reflection film in the opening; joining a surface of the embedded reflection film with the circuit board, and then removing the substrate; and forming, on the interlayer insulation film, a light emission unit including the first electrode, the organic layer, and the second electrode that are stacked.

(10) For achieving the above-described object, an electronic apparatus according to the present disclosure is an electronic apparatus including a display device in which more than one pixel is arranged in a two-dimensional matrix on a circuit board, the pixel including a light emission unit including a first electrode, an organic layer, and a second electrode that are stacked, in which in the display device, the first electrode is disposed for each light emission unit, and a partition is formed between the first electrode and an adjacent first electrode, the organic layer and the second

electrode are stacked on an entire surface including the first electrode and the partition, the first electrode is formed on an interlayer insulation film, and a reflection film is formed below the first electrode, the reflection film including a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film.

Description

BRIEF DESCRIPTION OF DRAWINGS

- (1) FIG. 1 is a schematic plan view of a display device according to a first embodiment of the present disclosure.
- (2) FIG. 2 is a schematic partial cross-sectional view of the display device according to the first embodiment.
- (3) FIGS. 3A and 3B are schematic partial end views for explaining a method for manufacturing the display device according to the first embodiment.
- (4) FIGS. 4A and 4B are schematic partial end views for explaining the method for manufacturing the display device according to the first embodiment, as continued from FIG. 3B.
- (5) FIG. 5 is a schematic partial end view for explaining the method for manufacturing the display device according to the first embodiment, as continued from FIG. 4B.
- (6) FIG. 6 is a schematic partial end view for explaining the method for manufacturing the display device according to the first embodiment, as continued from FIG. 5.
- (7) FIG. 7 is a schematic partial end view for explaining the method for manufacturing the display device according to the first embodiment, as continued from FIG. 6.
- (8) FIG. 8 is a schematic partial end view for explaining the method for manufacturing the display device according to the first embodiment, as continued from FIG. 7.
- (9) FIG. 9 is a schematic partial end view for explaining the method for manufacturing the display device according to the first embodiment, as continued from FIG. 8.
- (10) FIG. 10 is a schematic partial end view for explaining the method for manufacturing the display device according to the first embodiment, as continued from FIG. 9.
- (11) FIG. 11 is a schematic partial end view for explaining the method for manufacturing the display device according to the first embodiment, as continued from FIG. 10.
- (12) FIG. 12 is a schematic partial end view for explaining the method for manufacturing the display device according to the first embodiment, as continued from FIG. 11.
- (13) FIG. 13 is a schematic partial cross-sectional view of a display device according to a second embodiment.
- (14) FIGS. 14A and 14B are schematic partial end views for explaining a method for manufacturing the display device according to the second embodiment.
- (15) FIGS. 15A and 15B are schematic partial end views for explaining the method for manufacturing the display device according to the second embodiment, as continued from FIG. 14B.
- (16) FIG. 16 is a schematic partial end view for explaining the method for manufacturing the display device according to the second embodiment, as continued from FIG. 15B.
- (17) FIG. 17 is a schematic partial end view for explaining the method for manufacturing the display device according to the second embodiment, as continued from FIG. 16.
- (18) FIG. 18 is a schematic partial end view for explaining the method for manufacturing the display device according to the second embodiment, as continued from FIG. 17.
- (19) FIG. 19 is a schematic partial end view for explaining the method for manufacturing the display device according to the second embodiment, as continued from FIG. 18.
- (20) FIG. 20 is a schematic partial end view for explaining the method for manufacturing the

display device according to the second embodiment, as continued from FIG. 19.

(21) FIG. 21 is a schematic partial end view for explaining the method for manufacturing the display device according to the second embodiment, as continued from FIG. 20.

(22) FIG. 22 is a schematic partial end view for explaining the method for manufacturing the display device according to the second embodiment, as continued from FIG. 21.

(23) FIG. 23 is a schematic partial end view for explaining the method for manufacturing the display device according to the second embodiment, as continued from FIG. 22.

(24) FIG. 24 is a schematic partial end view for explaining the method for manufacturing the display device according to the second embodiment, as continued from FIG. 23.

(25) FIG. 25 is a schematic partial cross-sectional view of a display device according to a third embodiment.

(26) FIGS. 26A and 26B are schematic partial end views for explaining a method for manufacturing the display device according to the third embodiment.

(27) FIG. 27 is a schematic partial end view for explaining the method for manufacturing the display device according to the third embodiment, as continued from FIG. 26B.

(28) FIG. 28 is a schematic partial end view for explaining the method for manufacturing the display device according to the third embodiment, as continued from FIG. 27.

(29) FIG. 29 is a schematic partial end view for explaining the method for manufacturing the display device according to the third embodiment, as continued from FIG. 28.

(30) FIG. 30 is a schematic partial end view for explaining the method for manufacturing the display device according to the third embodiment, as continued from FIG. 29.

(31) FIG. 31 is a schematic partial end view for explaining the method for manufacturing the display device according to the third embodiment, as continued from FIG. 30.

(32) FIG. 32 is a schematic partial end view for explaining the method for manufacturing the display device according to the third embodiment, as continued from FIG. 31.

(33) FIG. 33 is a schematic partial end view for explaining the method for manufacturing the display device according to the third embodiment, as continued from FIG. 32.

(34) FIG. 34 is a schematic partial end view for explaining the method for manufacturing the display device according to the third embodiment, as continued from FIG. 33.

(35) FIG. 35 is a schematic partial end view for explaining a resonator structure in the display device according to the third embodiment.

(36) FIG. 36 is an external view of a lens-interchangeable single-lens reflex type digital still camera; FIG. 36A shows a front view thereof and FIG. 36B shows a rear view thereof.

(37) FIG. 37 is an external view of a head-mounted display.

(38) FIG. 38 is an external view of a see-through head-mounted display.

MODE FOR CARRYING OUT THE INVENTION

(39) With reference to the drawings, the present disclosure will now be described on the basis of embodiments. The present disclosure is not limited to the embodiments, and various numerical values and materials in the embodiments are examples. In the following description, the same elements or elements having the same functions will be denoted by the same reference symbols, and redundant descriptions will be omitted. Note that descriptions will be provided in the order mentioned below. 1. General description of a display device, a method for manufacturing a display device, and an electronic apparatus of the present disclosure 2. First embodiment 3. Second embodiment 4. Third embodiment 5. Description of electronic apparatus and others

General Description Of A Display Device, a Method for Manufacturing a Display Device, and an Electronic Apparatus of the Present Disclosure

(40) A display device according to the present disclosure, a display device used for an electronic apparatus according to the present disclosure, and a display device obtained by a method for manufacturing the display device according to the present disclosure (hereinafter may be simply referred to as a “display device of the present disclosure”) may have a configuration in which an

interlayer insulation film includes different types of two or more insulation materials stacked to be in contact with each other.

(41) In this case, the interlayer insulation film may include inorganic insulation materials such as silicon oxide (SiO.sub.x), silicon nitride (SiN.sub.x), or silicon oxynitride (SiO.sub.xN.sub.y), for example. The interlayer insulation film may be formed to include at least two types of layers selected from a layer of silicon oxide, a layer of silicon nitride, and a layer of silicon oxynitride. Moreover, the interlayer insulation film may be formed with two types of layers stacked alternately.

(42) In the display device of the present disclosure including various preferred configurations described above, the number of layers in the interlayer insulation film located between a reflection film and a first electrode may differ depending on the display color of the pixel.

(43) In the display device of the present disclosure including various preferred configurations described above, the film thickness of the interlayer insulation film located between the reflection film and the first electrode may be set to an optical distance that differs depending on the display color of the pixel. Moreover, the optical distance I may be needed to satisfy the following condition:

$$2L/\lambda + \Phi/2\pi = m \text{ (m is an integer)}$$

(44) where the symbol Φ represents the phase shift of reflected light generated in the first electrode and the reflection film, the symbol L represents the optical distance between the first electrode and the reflection film, and the symbol λ represents the peak wavelength of a spectrum of light taken from a pixel.

(45) In the display device of the present disclosure including preferred configurations described above, the reflection film may be embedded in an opening provided in the interlayer insulation film. This configuration has an advantage that the light reflecting surface is not exposed to the outside, thus creating no decrease in reflectance attributed to oxidation of a material included in the reflection film. The opening can be formed by, for example, performing an etching process such that a boundary plane where different insulation materials are in contact with each other in the interlayer insulation film serves as a stopper. Specifically, the process is only needed to be performed by selecting an appropriate combination of a material included in the interlayer insulation film with an etchant so that a certain insulation material acts as a stopper.

(46) In the display device of the present disclosure including preferred configurations described above, the reflection film may include a metal material such as silver (Ag), a silver alloy, aluminum (Al), an aluminum alloy, platinum (Pt), gold (Au), chromium (Cr), tungsten (W), and the like. In this case, from the viewpoint of obtaining a high reflectance, the reflection film preferably includes silver or a silver alloy. Assuming that the decrease in reflectance attributed to oxidation is sufficiently suppressed, the reflection film including silver exhibits a reflectance of approximately 90 percent or more in a visible light region. The thickness of the reflection film is preferably set to a range of 100 to 300 nanometers.

(47) In an alternative configuration, the reflection film may have an upper layer portion and a lower layer portion, the upper layer portion including silver or a silver alloy, and the lower layer portion including copper or a copper alloy. In a case where an electrode or the like is formed in a portion of a circuit board facing the reflection film, the electrode often includes copper or a copper alloy. In this case, using copper or a copper alloy to form the lower layer portion of the reflection film can improve the bondability between the circuit board side and the reflection film side.

(48) In the display device of the present disclosure including preferred configurations described above, the circuit board may include a drive circuit for driving a pixel, and the first electrode and the drive circuit may be electrically connected. The first electrode and the drive circuit may be directly connected through a conductive portion including, for example, a via or the like provided in the interlayer insulation film. Alternatively, the first electrode and the drive circuit may be electrically connected through the reflection film.

(49) In the display device of the present disclosure, the light emission unit may be of a so-called

top emission type. The light emission unit is formed by sandwiching an organic layer, which includes a hole transport layer, a light emission layer, an electron transport layer, and the like, between the first electrode and the second electrode. In a case where the cathode is shared, the second electrode is the cathode electrode and the first electrode is the anode electrode.

(50) The display device of the present disclosure including preferred configurations described above may be configured to provide color display. In the case of color display, a color filter can be formed by using, for example, a resin material containing a pigment or a dye. Note that the display device may be configured to provide so-called monochrome display in some cases.

(51) In the case of a color display configuration, a single pixel may include a plurality of sub-pixels. Specifically, a single pixel may include three sub-pixels: a red display sub-pixel, a green display sub-pixel, and a blue display sub-pixel. Moreover, a single pixel may include a set of sub-pixels in which one or more types of sub-pixels are added to these three types of sub-pixels (for example, a set in which a sub-pixel that emits white light for higher brightness is added, a set in which a sub-pixel that emits complementary color light for expanding a color reproduction range is added, a set in which a sub-pixel that emits yellow light for expanding a color reproduction range is added, or a set in which sub-pixels that emit yellow light and cyan light for expanding a color reproduction range are added).

(52) Examples of pixel values of the display device may include, without limitation, some resolutions for image display such as VGA (640, 480), S-VGA (800, 600), XGA (1024, 768), APRC (1152, 900), S-XGA (1280, 1024), U-XGA (1600, 1200), HD-TV (1920, 1080), (D-XGA (2048, 1536), as well as (1920, 1035), (720, 480), (1280, 960), and the like.

(53) A partition can be formed by using a material appropriately selected from known inorganic materials and organic materials, and can be formed by, for example, a combination of a well-known film forming method such as a physical vapor deposition method (PVD method) exemplified by a vacuum evaporation method and a sputtering method, various chemical vapor deposition methods (CVD methods), and the like with a well-known patterning method such as an etching method, a lift-off method, and the like.

(54) In the display device according to the present disclosure, the configuration of the drive circuit or the like that controls light emission from the light emission unit is not particularly limited. The light emission unit may be formed on a certain plane over the circuit board and, for example, disposed via the interlayer insulation layer above the drive circuit that drives the light emission unit. The configuration of the transistor included in the drive circuit is not particularly limited. The transistor may be a p-channel type field effect transistor or an n-channel type field effect transistor.

(55) Examples of a material included in the circuit board may include a semiconductor material, a glass material, or a plastic material. In a case where the drive circuit includes a transistor formed on a semiconductor substrate, for example, a well region is only needed to be disposed on the semiconductor substrate including silicon and the transistor is only needed to be formed in the well. On the other hand, in a case where the drive circuit includes a thin film transistor or the like, the drive circuit can be formed by forming a semiconductor thin film on a substrate that includes a glass material or a plastic material. Various types of wiring may have a well-known configuration and structure.

(56) The first electrode is disposed on the circuit board for each light emission unit. In a case where the cathode is shared, the first electrode functions as the anode electrode for the light emission unit. The first electrode may include, for example, a transparent conductive material such as indium zinc oxide, indium tin oxide, or the like. Alternatively, the first electrode may include a metal, an alloy, or the like to be formed to be thin enough to have light transmissibility.

(57) The organic layer includes an organic light emission material and, as a common continuous film, is disposed on the first electrode and on the partition. The organic layer emits light when a voltage is applied between the first electrode and the second electrode. The organic layer may have a structure in which, for example, a hole injection layer, a hole transport layer, a light emission

layer, an electron transport layer, and an electron injection layer are stacked in the order mentioned from the first electrode side. A hole transport material, a hole transport material, an electron transport material, and an organic light emission material included in the organic layer are not particularly limited and a well-known material can be used.

(58) The organic layer may have a so-called tandem structure in which a plurality of light emission layers is connected via a charge generation layer or an intermediate electrode. For example, a light emission unit that emits white light can be formed by stacking light emission layers that emit red light, green light, and blue light, or by stacking light emission layers that emit yellow light and blue light.

(59) The second electrode is disposed as a common continuous film on the organic layer. The second electrode preferably includes a material that has high light transmissibility and a low work function. For example, the second electrode can be formed by using a transparent conductive material such as indium tin oxide (IT), indium zinc oxide (IZO), zinc oxide, aluminum-doped zinc oxide, or gallium-doped zinc oxide. Alternatively, the second electrode may include magnesium (Mg), silver (Ag), an alloy thereof, or the like to be formed to be thin enough to have light transmissibility. The thickness of the second electrode is preferably set to a range of about 3 to 15 nanometers. Furthermore, the second electrode may include a multilayer film in some cases. For example, a first layer may include calcium (Ca), barium (Ba), lithium (Li), cesium (Cs), indium (In), magnesium (Mg), silver (Ag), or the like, while a second layer may include magnesium (Mg), silver (Ag), an alloy thereof, or the like.

(60) A condition shown in each of a variety of formulas herein is satisfied not only in a case where the formula is mathematically precisely satisfied but also in a case where the formula is substantially satisfied. For a formula to be satisfied, various variations occurring in the design or manufacture of the display element, the display panel, or the like are permitted to be present. Furthermore, the drawings referred to in the following description are schematic drawings. For example, FIG. 2 described later shows a cross-sectional structure of the display device, but does not indicate ratios of width, height, thickness, and the like.

First Embodiment

(61) The first embodiment relates to a display device, a method for manufacturing a display device, and an electronic apparatus according to a first aspect of the present disclosure.

(62) FIG. 1 is a schematic plan view of a display device according to a first embodiment of the present disclosure. The display device **1** includes a display region **11** in which pixels **10** each including a light emission unit ELP and a drive circuit that drives the light emission unit ELP are arranged in a two-dimensional matrix while being connected to a scanning line SCL extending along the row direction (X direction in FIG. 1) and to a data line DTL extending along the column direction (Y direction in FIG. 1), and also includes a power supply unit **100** that supplies voltages to a power supply line PS1, a scanning unit **101** that supplies scanning signals to the scanning line SCL, and a data driver **102** that supplies signal voltages to the data line DTL. Note that FIG. 1 shows a single pixel **10** for convenience of illustration, or more specifically, FIG. 1 shows a connection relationship in the (q, p)-th pixel **10** as described later.

(63) The display device **1** further includes a common power supply line PS2 that is connected to all the pixels **10** in common. A predetermined drive voltage is supplied from the power supply unit **100** to the power supply line PS1, while a common voltage (a ground potential, for example) is supplied to the common power supply line PS2.

(64) Although not illustrated in FIG. 1, the display region **11** includes a total of $Q \times P$ pixels (display elements) **10**, namely Q pixels along the row direction and P pixels along the column direction, arranged in a two-dimensional matrix. In the display region, the number of rows of the pixels **10** is P and the number of pixels **10** constituting each row is Q.

(65) Furthermore, the number of the scanning lines SCL and the number of power supply lines PS1 are each P. The pixels **10** in the p-th row (where $p=1, 2, \dots, P$) are connected to the p-th scanning

line SCL.sub.p and the p-th power supply line PS1.sub.p to constitute a single display element row. Note that FIG. 1 shows the scanning line SCL.sub.p and the power supply line PS1.sub.p only.

(66) Furthermore, the number of the data lines DTL is Q. The pixels **10** in the q-th column (where $q=1, 2, \dots, Q$) are connected to the q-th data line DTL.sub.q. Note that FIG. 1 shows the data line DTL.sub.q only.

(67) The display device **1** is, for example, a color display device. A single pixel **10** constitutes a single sub-pixel. The display device **1** is line-sequentially scanned row by row in response to a scanning signal from the scanning unit **101**. The pixel **10** located in the p-th row and the q-th column is hereinafter referred to as a (q, p)-th pixel **10** or the (q, p)-th pixel **10**.

(68) In the display device **1**, Q pixels **10** arranged in the p-th row are simultaneously driven. In other words, in the Q pixels **10** arranged along the row direction, the timing of light emission/non-emission is controlled for each row to which the pixels belong. Assuming that the display frame rate of the display device **1** is denoted by FR (times/second), the scanning period (so-called, horizontal scanning period) per row when the display device **1** is line-sequentially scanned row by row is less than $(1/FR) \times (1/P)$ seconds.

(69) The pixel **10** includes the light emission unit ELP and the drive circuit that drives the light emission unit ELP. The light emission unit ELP includes an organic electroluminescent light emission unit. The drive circuit includes a write transistor TR.sub.W, a drive transistor TR.sub.D and a capacitance unit C.sub.1. When a current flows through the light emission unit ELP via the drive transistor TR.sub.D, the light emission unit ELP emits light. Each transistor includes a p-channel type field effect transistor.

(70) In the pixel **10**, one source/drain region of the drive transistor TR.sub.D is connected to one end of the capacitance unit C.sub.1 and to the power supply line PS1, while the other source/drain region is connected to one end (specifically, the anode electrode) of the light emission unit ELP. The gate electrode of the drive transistor TR.sub.D is connected to the other source/drain region of the write transistor TR.sub.W and is also connected to the other end of the capacitance unit C.sub.1.

(71) Furthermore, in the write transistor TR.sub.W, one source/drain region is connected to the data line DTL and the gate electrode is connected to the scanning line SCL.

(72) The other end (specifically, the cathode electrode) of the light emission unit ELP is connected to the common power supply line PS2. A predetermined cathode voltage V.sub.Cat is supplied to the common power supply line PS2. Note that the capacitance of the light emission unit ELP is denoted by the symbol C.sub.EL.

(73) The following describes driving of the pixel **10** in outline. When the write transistor TR.sub.W is caused to become conductive by a scanning signal from the scanning unit **101** while a voltage corresponding to the brightness of the image to be displayed is supplied from the data driver **102** to the data line DTL, the voltage corresponding to the brightness of the image to be displayed is written to the capacitance unit C.sub.1. After the write transistor TR.sub.W is caused to become non-conductive, a current flows through the drive transistor TR.sub.D in accordance with the voltage held in the capacitance unit C.sub.1, whereby the light emission unit ELP emits light.

(74) Note that, in the present disclosure, the configuration of the drive circuit that controls light emission of the pixel **10** is not particularly limited. Therefore, the configuration illustrated in FIG. 1 is merely an example, and the display device according to the present embodiment may have various configurations.

(75) The following describes a detailed structure of the display device **1**.

(76) FIG. 2 is a schematic partial cross-sectional view of the display device according to the first embodiment.

(77) In the display device **1**, the light emission unit ELP includes a first electrode **41**, an organic layer **60**, and a second electrode **70**, which are stacked together. The first electrode **41** is disposed for each light emission units ELP, and a partition **51** is formed between adjacent first electrodes **41**. In addition, the organic layer **60** and the second electrode **70** are stacked over the entire surface

including the first electrode **41** and the partition **51**. Moreover, a protection film **80** is disposed on the entire surface including the second electrode **70**, and a color filter **90** is placed on the protection film **80**. The reference numeral **91** denotes a portion of a light shielding region, and the reference numeral **92** denotes a portion of a filter region.

(78) The first electrode **41** is formed on an interlayer insulation film **30**. Below the first electrode **41**, there is formed a reflection film **31** that has a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film **30**.

(79) The film thickness of the interlayer insulation film **30** located between the reflection film **31** and the first electrode **41** is set such that light with a wide wavelength band ranging from blue to red can be taken out from the pixel.

(80) Various components will now be described in detail with reference to FIG. 2.

(81) The circuit board **20** includes: a base material **21**; a gate electrode **22** formed on the base material **21**; a gate insulation film **23** formed to cover the entire surface of the gate electrode **22**; a semiconductor material layer **24**; a planarization film **25** formed to cover the entire surface including the semiconductor material layer **24**; a source/drain electrode **26** connected to a source/drain region of a transistor formed in the semiconductor material layer **24**; a planarization film **27** formed to cover the entire surface including the source/drain electrode **26**; and a contact plug **28** that is disposed in an opening in the planarization film **27** and is connected to the source/drain electrode **26** of the drive transistor.

(82) The circuit board **20** is equipped with a drive circuit including the transistor and others described above for driving the pixel **10**. In addition, the first electrode **41** and the drive circuit are electrically connected. More specifically, the first electrode **41** is connected to the source/drain electrode **26** of the transistor formed in the semiconductor material layer **24** via the conductive portion **33** connected to the contact plug **28**.

(83) The base material **21** may include, for example, a glass material, a semiconductor material, a plastic material, or the like. The drive circuit including a thin film transistor that controls light emission of the light emission unit ELP is formed on the base material **21**.

(84) The gate electrode **22** for various transistors included is the drive circuit may be formed by using, for example, aluminum (Al) or some other metal, polysilicon, or the like. The gate insulation film **23** is disposed on the entire surface of the base material **21** so as to cover the gate electrode **22**. The gate insulation film **23** can be formed by using, for example, silicon oxide (SiO₂), silicon nitride (SiN_x), or the like.

(85) The semiconductor material layer **24** can be formed on the gate insulation film **23** by using, for example, amorphous silicon, polycrystalline silicon, an oxide semiconductor, or the like. Furthermore, some regions of the semiconductor material layer **24** are doped with an impurity to form a source/drain region. Moreover, the semiconductor material layer **24** includes a region that is located between one source/drain region and the other source/drain region and above the gate electrode **22** to form a channel region. With these components, a bottom-gate type thin film transistor is disposed on the base material **21**. Note that illustration of the source/drain regions and the channel region is omitted in FIG. 2.

(86) The planarization film **25** is disposed on the semiconductor material layer **24**. The planarization film **25** includes, for example, silicon oxide (SiO₂), silicon nitride (SiN_x), silicon oxynitride (SiO_xN_y), or the like. The source/drain electrode **26** is connected to the semiconductor material layer **24** via a contact hole provided in the planarization film **25**. The source/drain electrode **26** includes a metal such as, for example, aluminum (Al).

(87) The planarization film **27** is formed for the purpose of covering and planarizing the drive circuit and others. The planarization film **27** can be formed by using, for example, an organic insulation film such as a polyimide-based resin, an acrylic-based resin, or a novolak-based resin, or an inorganic insulation film such as silicon oxide (SiO₂), silicon nitride (SiN_x), or silicon

oxynitride (Si.sub.xN.sub.y).

(88) The contact plug **28** includes a metal material such as, for example, copper (Cu) or a copper alloy, and is formed in an opening provided in the planarization film **27**. The first electrode **41** and the contact plug **28** are electrically connected by the conductive portion **33** formed in an opening provided in the interlayer insulation film **30**, which is described below.

(89) The interlayer insulation film **30** includes different types of a plurality of insulation materials stacked to be in contact with each other. In the example illustrated in FIG. **2**, the interlayer insulation film **30** is formed by stacking a first layer **30A**, a second layer **30B**, and a third layer **30C**.

(90) The interlayer insulation film **30** can be formed by using an inorganic insulation material or the like. The interlayer insulation film **30** may be formed to include at least two types of layers selected from, for example, a layer of silicon oxide, a layer of silicon nitride, and a layer of silicon oxynitride, or may be formed with two types of layers stacked alternately. The following description is provided on the assumption that the interlayer insulation film **30** includes a layer of silicon oxide and a layer of silicon nitride.

(91) The reflection film **31**, which is disposed below the first electrode **41**, is formed to have a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film **30**. More specifically, the light reflecting surface of the reflection film **31** is formed to be flush with the boundary plane on which the first layer **30A** and the second layer **30B** are in contact with each other in the interlayer insulation film **30**.

(92) The reflection film **31** is embedded in an opening provided in the interlayer insulation film **30**. The reflection film **31** includes a metal material. The description is provided here on the assumption that the reflection film **31** includes silver or a silver alloy. Note that the reference numeral **32** denotes a filling member that fills an opening in the reflection film **31** on the circuit board **20** side. From the viewpoint of bondability to the circuit board **20**, the filling member **32** is formed by using the same material as the material of the planarization film **27**.

(93) More specifically, the reflection film **31** is embedded in the opening provided in the interlayer insulation film **30** with the first layer **30A** serving as a stopper film. Thus, the position of the light reflecting surface of the reflection film **31** is defined by the thickness of a layer included in the interlayer insulation film **30**. The film thickness of a layer included in the interlayer insulation film **30** and the film thickness of the organic layer **60** can be controlled with high precision by a film forming process. As a result, the dimension between the light reflecting surface of the reflection film **31** and the second electrode **70** (the portion indicated by an arrow in FIG. **2**) can be set with high precision.

(94) Furthermore, for example, it is made possible to reduce the stray light to an adjacent pixel by adjusting the composition of the second layer **30B** in the interlayer insulation film **30** so that the light shielding rate is set to a higher value relative to the first layer **30A**.

(95) The first electrode **41** is formed on an interlayer insulation film **30**. The first electrode **41** includes a transparent conductive material such as ITO, for example. The thickness of the first electrode **41** is preferably set to a range of 20 to 200 nanometers.

(96) The organic layer **60** is formed on the entire surface including the first electrode **41** and the partition **51**. The organic layer **60** is a white light emission functional layer that emits white light, and may have a structure in which a hole injection layer, a hole transport layer, a red light emission layer, a light emission separation layer, a blue light emission layer, a green light emission layer, and an electron transport layer, which include an organic material, are sequentially stacked, for example. Alternatively, the organic layer **60** may have a structure in which a hole injection layer, a hole transport layer, a blue light emission layer, an electron transport layer, a charge generation layer, a hole injection layer, a hole transport layer, a yellow light emission layer, and an electron transport layer are sequentially stacked from the bottom layer. Note that the organic layer **60** has a

multilayer structure, but is illustrated as a single layer in the figure.

(97) The second electrode **70** is formed on the entire surface including the organic layer **60**. The second electrode **70** includes a material that has high light transmissibility and a low work function. The description is provided here on the assumption that the second electrode **70** includes ITO.

(98) The protection film **80** is formed on the entire surface including the second electrode **70**. The protection film **80**, which is intended to prevent moisture from entering the organic layer **60**, includes a material having low water permeability and is formed to have a thickness of about 1 to 8 micrometers. As a material of the protection film **80**, silicon nitride (SiN.sub.x), silicon oxide (SiO.sub.x), aluminum oxide (AlO.sub.x), titanium oxide (TiO.sub.x), or a combination thereof is used.

(99) The color filter **90** is formed on, for example, a counter substrate side (not illustrated), and is stuck on the protection film **80** with an ultraviolet curable resin, a thermosetting resin, or the like. Through the color filter **90**, the light emitted by the light emission unit ELP is color-separated and taken.

(100) The foregoing has described a detailed structure of the display device **1**. The above-described display device **1** can be manufactured as follows.

(101) The following describes a method for manufacturing the display device **1** described above. The method for manufacturing the display device **1** includes the steps of: forming, on a substrate, an interlayer insulation film in which layers of different types of insulation materials are stacked to be in contact with each other; forming an opening in a region of the interlayer insulation film, the region corresponding to a first electrode, in such a way that a plane flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film is exposed to a bottom; embedding a reflection film in the opening; joining a surface of the embedded reflection film with a circuit board, and then removing the substrate; and forming, on the interlayer insulation film, a light emission unit in which the first electrode, an organic layer, and a second electrode are stacked. The same applies to other embodiments described later.

(102) FIGS. **3** to **12** are schematic partial end views for explaining the method for manufacturing the display device according to the first embodiment.

(103) The method for manufacturing the display device **1** will now be described in detail with reference to these drawings.

(104) Step-100 (see FIG. **3A**)

(105) First, the circuit board **20** on which a drive circuit is formed is prepared. The base material **21** is prepared, and then the base material **21** is subjected to a predetermined film forming and patterning process, whereby the drive circuit including a thin film transistor is formed. Then, the planarization film **27** is formed on the entire surface of the drive circuit by a spin coating method, a slit coating method, a sputtering method, a CVD method, or the like. Next, an opening is formed in the planarization film **27**, and then the contact plug **28** is formed in the opening, whereby the circuit board **20** illustrated in FIG. **3A** can be obtained.

(106) Subsequently, the interlayer insulation film **30** having the reflection film **31** formed therein is disposed on the circuit board **20** by the procedure illustrated in FIGS. **3B** to **7**.

(107) Step-110 (see FIG. **3B**)

(108) A substrate **39** of a silicon wafer is prepared, and the interlayer insulation film **30** is formed thereon by, for example, stacking two types of layers alternately, such as a layer of silicon oxide and a layer of silicon nitride (see FIG. **3B**). In the example shown in the figure, the first layer **30A** and the third layer **30C** are layers of silicon oxide and the second layer **30B** is a layer of silicon nitride.

(109) Step-120 (see FIG. **4A**)

(110) Then, an opening OP**31** is formed in the interlayer insulation film **30** in a portion corresponding to the reflection film **31** such that the boundary plane between the first layer **30A** and the second layer **30B** is exposed to the bottom (see FIG. **4A**). The opening OP**31** can be formed

by, for example, performing dry etching under the condition that the first layer **30A** acts as a stopper film. Furthermore, at the same time, an opening **OP33** is formed in the interlayer insulation film **30** in a portion corresponding to the conductive portion **33** so as to penetrate through the interlayer insulation film **30**. The opening **OP33** can be formed by, for example, performing dry etching under the condition that the substrate **39** acts as a stopper.

(111) Step-130 (see FIG. **4B**)

(112) Then, the reflection film **31** and others are formed in the opening **OP31**, while the conductive portion **33** is formed in the opening **OP33**. For example, a silver thin film is formed on the entire surface including the opening by a sputtering method, and then the filling member **32** to fill the opening of the reflection film **31** is formed, followed by planarization carried out by using, for example, a CMP method.

(113) Step-140 (see FIGS. **5**, **6**, and **7**)

(114) Subsequently, with the interlayer insulation film **30** and the circuit board **20** facing each other (see FIG. **5**), the interlayer insulation film **30** and the circuit board **20** are joined together. For example, the facing surfaces of the interlayer insulation film **30** and the circuit board **20** are activated by removing the inert layer on each surface by irradiating the inert layer with energy waves such as plasma or accelerated ion beams under an ultra-high vacuum. Then, the surface-activated substances are brought into close contact with each other, whereby the interlayer insulation film **30** and the circuit board **20** can be joined together by as atomic force (see FIG. **6**). Then, the substrate **39** is removed (see FIG. **7**).

(115) Next, the light emission unit **ELP** and others are formed on the interlayer insulation film **30** by the procedure illustrated in FIGS. **8** to **12**.

(116) Step-150 (see FIG. **8**)

(117) First, the first electrode **41** is formed on the interlayer insulation film **30**. The first electrode **41** can be obtained by, for example, forming an ITO film on the interlayer insulation film **30** and then patterning the ITO film.

(118) Step-160 (see FIG. **9**)

(119) Next, the partition **51** serving as an inter-pixel insulation film is formed between the first electrode **41** and the first electrode **41**. An inorganic insulation film such as silicon oxynitride is formed on the entire surface including the first electrode **41** by a sputtering method, a CVD method, or the like. Subsequently, a pixel opening is patterned by a lithography method and a dry etching method so that the formed inorganic insulation film has a predetermined recess, whereby the partition **51** can be formed.

(120) Step-170 (see FIG. **10**)

(121) Next, the organic layer **60** that emits white light is formed on the entire surface including the first electrode **41** serving as an anode electrode by, for example, sequentially forming a hole injection layer, a hole transport layer, a red light emission layer, a light emission separation layer, a blue light emission layer, a green light emission layer, and an electron transport layer.

(122) Step-180 (see FIGS. **11** and **12**)

(123) Next, the second electrode **70** serving as a cathode electrode is formed on the entire surface of the organic layer **60**. The second electrode **70** can be obtained by, for example, forming a film of a silver-magnesium alloy on the entire surface by a vapor deposition method (see FIG. **11**). After that, the protection film **80** is formed on the entire surface, and then the counter substrate on which the color filter **90** is formed is stuck thereto, whereby the display device **1** can be obtained (see FIG. **12**).

(124) The distance between the light reflecting surface of the reflection film **31** and the second electrode **70** is defined by the thicknesses of the organic layer **60**, the first electrode **41**, and the first layer **30A** of the interlayer insulation film **30**. These film thicknesses can be controlled with high precision due to the process of forming the components. Therefore, since the positional relationship between the organic layer and the reflection film can be set with high precision, variations in color

and the like can be suppressed.

(125) In addition, the light reflecting surface of the reflection film **31** is formed by embedding a metal material in the interlayer insulation film **30**. Therefore, the light reflecting surface is not exposed to the outside air. For this reason, a material that has a high reflectance but is prone to oxidization, such as silver or a silver alloy, can be used as a material for forming the reflection film **31** without trouble.

(126) Note that, in some cases, a mode in which a thin film of a transparent conductive material such as ITO is formed in the opening provided is the interlayer insulation film **30** and then a metal material is embedded may be carried out.

Second Embodiment

(127) The second embodiment is a modification of the first embodiment. In the first embodiment, the first electrode **41** is connected to the drive circuit that drives the pixel **10** via the conductive portion **33** connected to the contact plug **28**. In the second embodiment, the first electrode and the drive circuit are electrically connected via the reflection film, which is a major difference.

(128) FIG. **13** is a schematic partial cross-sectional view of a display device according to a second embodiment. Note that a schematic plan view of the display device according to the second embodiment is found in FIG. **1** by replacing the display device **1** with the display device **2**.

(129) The display device **2** is different from the display device **1** in shape and configuration of a contact plug **228**, a reflection film **231**, a filling member **232**, and a conductive portion **233**.

(130) The contact plug **228** is formed to have a surface facing the reflection film **231**, the surface being shaped to cover the reflection film **231**. In addition, the reflection film **231** is connected to the source/drain electrode **26** of the drive transistor via the contact plug **228**.

(131) The reflection film **231**, which is disposed below the first electrode **41**, is formed to have a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film **30**. As in the first embodiment, the light reflecting surface of the reflection film **231** is formed to be flush with the boundary plane on which the first layer **30A** and the second layer **30B** are in contact with each other in the interlayer insulation film **30**.

(132) The reflection film **231** is embedded in an opening provided in the interlayer insulation film **30**. Note that the reference numeral **232** denotes a filling member that fills an opening in the reflection film **231** on the circuit board **20** side. From the viewpoint of bondability to the circuit board **20**, the filling member **232** is formed by using the same material as the material of the contact plug **228**. Therefore, the filling member **232** substantially forms a lower layer portion of the reflection film. The reflection film has an upper layer portion and a lower layer portion, the upper layer portion including silver or a silver alloy, and the lower layer portion including copper or a copper alloy.

(133) In the configuration illustrated in FIG. **13**, the reflection film **231** and the contact plug **228** are electrically connected. In addition, the first electrode **41** and the reflection film **231** are electrically connected by the conductive portion **233** formed in an opening provided in the interlayer insulation film **30**. In this way, the first electrode **41** and the drive circuit are electrically connected via the reflection film **231**.

(134) The foregoing has described a detailed structure of the display device **2**. The above-described display device **2** can be manufactured as follows.

(135) FIGS. **14** to **24** are schematic partial end views for explaining the method for manufacturing the display device according to the second embodiment.

(136) Step-200 (see FIG. **14A**)

(137) First, a circuit board **220** on which a drive circuit is formed is prepared. The base material **21** is prepared, and then the base material **21** is subjected to a predetermined film forming and patterning process, whereby the drive circuit including a thin film transistor is formed. Then, the planarization film **27** is formed on the entire surface of the drive circuit by a spin coating method, a

slit coating method, a sputtering method, a CVD method, or the like. Next, arm opening is formed in the planarization film **27**, and then the contact plug **228** is formed in the opening, whereby the circuit board **220** illustrated in FIG. **14A** can be obtained.

(138) Subsequently, the interlayer insulation film **30** having the reflection film **231** formed therein is disposed on the circuit board **220** by the procedure illustrated in FIGS. **14B** to **18**.

(139) Step-210 (see FIG. **14B**)

(140) The substrate **39** of a silicon wafer is prepared, and the interlayer insulation film **30** is formed thereon by, for example, stacking two types of layers alternately, such as a layer of silicon oxide and a layer of silicon nitride (see FIG. **14B**). The composition of the interlayer insulation film **30** is similar to the composition described in [Step-110] above, and thus the description thereof is omitted.

(141) Step-220 (see FIG. **15A**)

(142) Then, an opening OP**231** is formed in the interlayer insulation film **30** in a portion corresponding to the reflection film **231** such that the boundary plane between the first layer **30A** and the second layer **30B** is exposed to the bottom (see FIG. **15A**). The opening OP**231** can be formed by, for example, performing dry etching under the condition that the first layer **30A** acts as a stopper film.

(143) Step-230 (see FIG. **15B**)

(144) After that, the reflection film **231** and others are formed in the opening OP**231**. For example, a silver thin film is formed on the entire surface including the opening OP**231** by a sputtering method, and then the filling member **232** to fill the opening of the reflection film **231** is formed, followed by planarization carried out by using, for example, a CMP method.

(145) Step-240 (see FIGS. **16**, **17**, and **18**)

(146) Subsequently, with the interlayer insulation film **30** and the circuit board **220** facing each other (see FIG. **16**), the interlayer insulation film **30** and the circuit board **220** are joined together. For example, the facing surfaces of the interlayer insulation film **30** and the circuit board **220** are activated by removing the inert layer on each surface by irradiating the inert layer with energy waves such as plasma or accelerated ion beams under an ultra-high vacuum. Then, the surface-activated substances are brought into close contact with each other, whereby the interlayer insulation film **30** and the circuit board **220** can be joined together by anatomic force (see FIG. **17**). Then, the substrate **39** is removed (see FIG. **18**).

(147) Step-250 (see FIGS. **19** and **20**)

(148) Next, an opening OP**233** is formed in the interlayer insulation film **30** in a portion corresponding to the conductive portion **233**. The opening OP**233** can be formed by, for example, performing dry etching under the condition that the reflection film **231** acts as a stopper (see FIG. **19**). After that, the conductive portion **233** is formed in the opening OP**233**. The conductive portion **233** can be formed by, for example, forming a conductive film on the entire surface and then performing planarization by using, for example, a CMP method (see FIG. **20**).

(149) Next, the light emission unit ELP and others are formed on the interlayer insulation film **30** by the procedure illustrated in FIGS. **21** to **24**.

(150) Step-260 (see FIG. **21**)

(151) First, the first electrode **41** is formed on the interlayer insulation film **30**. The first electrode **41** can be obtained by, for example, forming an ITO film on the interlayer insulation film **30** and then patterning the ITO film. The first electrode **41** and the reflection film **231** are electrically connected via the conductive portion **233**.

(152) Step-270 (see FIG. **22**)

(153) Next, the partition **51** serving as an inter-pixel insulation film is formed between the first electrode **41** and the first electrode **41**. The step is similar to the step described in [Step-160] above, and thus the description thereof is omitted.

(154) Step-280 (see FIG. **23**)

(155) Next, the organic layer **60** that emits white light is formed on the entire surface including the first electrode **41** serving as an anode electrode by, for example, sequentially forming a hole injection layer, a hole transport layer, a red light emission layer, a light emission separation layer, a blue light emission layer, a green light emission layer, and an electron transport layer.

(156) Step-290 (see FIG. **24**)

(157) Next, the second electrode **70** serving as a cathode electrode is formed on the entire surface of the organic layer **60**. The second electrode **70** can be obtained by, for example, forming a film of a silver-magnesium alloy on the entire surface by a vapor deposition method. After that, the protection film **80** is formed on the entire surface, and then the counter substrate on which the color filter **90** is formed is stuck thereto, whereby the display device **2** illustrated in FIG. **13** can be obtained.

(158) The distance between the light reflecting surface of the reflection film **231** and the second electrode **70** in the display device **2** is also defined by the thicknesses of the organic layer **60**, the first electrode **41**, and the first layer **30A** of the interlayer insulation film **30**. These film thicknesses can be controlled with high precision due to the process of forming the components. Therefore, since the positional relationship between the organic layer and the reflection film can be set with high precision, variations in color and the like can be suppressed.

(159) In addition, the light reflecting surface of the reflection film **231** is formed by embedding a metal material in the interlayer insulation film **30**. Therefore, the light reflecting surface is not exposed to the outside air. For this reason, a material that has a high reflectance but is prone to oxidization, such as silver or a silver alloy, can be used as a material for forming the reflection film **231** without trouble.

(160) Furthermore, the filling member **232** in the reflection film **231** and the contact plug **228** are made by using the same material. Therefore, when the interlayer insulation film **30** and the circuit board **220** are joined together, the contact plug **228** and the reflection film **231** are electrically joined favorably.

Third Embodiment

(161) The third embodiment is also a modification of the first embodiment. In the third embodiment, the number of layers in the interlayer insulation film located between the reflection film and the first electrode differs depending on the display color of the pixel, which is a major difference.

(162) FIG. **25** is a schematic partial cross-sectional view of a display device according to a third embodiment. Note that a schematic plan view of the display device according to the third embodiment is found in FIG. **1** by replacing the display device **1** with the display device **3**.

(163) The display device **3** is different from the display device **1** in shape and configuration of an interlayer insulation film **330**, a reflection film **331**, and a conductive portion **333**.

(164) As in the first embodiment, the interlayer insulation film **330** includes different types of a plurality of insulation materials that are stacked to be in contact with each other. In the example illustrated in FIG. **25**, the interlayer insulation film **330** is formed by stacking a first layer **330A**, a second layer **330B**, a third layer **330C**, a fourth layer **330D**, and a fifth layer **330E**.

(165) The interlayer insulation film **330** can be formed by using an inorganic insulation material or the like. The interlayer insulation film **330** may be formed to include at least two types of layers selected from, for example, a layer of silicon oxide, a layer of silicon nitride, and a layer of silicon oxynitride, or may be formed with two types of layers stacked alternately. The following description is provided on the assumption that the interlayer insulation film **330** includes a layer of silicon oxide and a layer of silicon nitride.

(166) The reflection film **331**, which is disposed below the first electrode **41**, is formed to have a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film **330**. In addition, the number of layers in the interlayer insulation film **330** located between the reflection film **331** and

the first electrode **41** differs depending on the display color of the pixel **10**.

(167) Specifically, the light reflecting surface of the reflection film **331A** used for the pixel **10** for blue display is formed to be flush with the boundary plane on which the first layer **330A** and the second layer **330B** are in contact with each other in the interlayer insulation film **330**. Accordingly, the number of layers in the interlayer insulation film **330** located between the reflection film **331A** and the first electrode **41** is one. The reflection film **331A** is embedded in the opening provided in the interlayer insulation film **330** with the first layer **330A** serving as a stopper film.

(168) The light reflecting surface of the reflection film **331B** used for the pixel **10** for green display is formed to be flush with the boundary plane on which the second layer **330B** and the third layer **330C** are in contact with each other in the interlayer insulation film **330**. Accordingly, the number of layers in the interlayer insulation film located between the reflection film **331B** and the first electrode **41** is two. The reflection film **331B** is embedded in the opening provided in the interlayer insulation film **330** with the second layer **330B** serving as a stopper film.

(169) The light reflecting surface of the reflection film **331C** used for the pixel **10** for red display is formed to be flush with the boundary plane on which the third layer **330C** and the fourth layer **330D** are in contact with each other in the interlayer insulation film **330**. Accordingly, the number of layers in the interlayer insulation film located between the reflection film **331C** and the first electrode **41** is three. The reflection film **331C** is embedded in the opening provided in the interlayer insulation film **330** with the third layer **330C** serving as a stopper film.

(170) The film thickness of the interlayer insulation film **330** located between the reflection film **331** and the first electrode **41** is set to an optical distance in accordance with the display color of the pixel **10**. The optical distance L is set so as to satisfy the following condition:

$$2L/\lambda + \Phi/2\pi = m \quad (m \text{ is an integer})$$

(171) where the symbol Φ represents the phase shift of reflected light generated in the first electrode **41** and the reflection film **330**, the symbol L represents the optical distance between the first electrode **41** and the reflection film **331**, and the symbol λ represents the peak wavelength of a spectrum of light taken from the pixel **10**.

(172) As described above, the reflection film **331** is embedded in the opening provided in the interlayer insulation film **330**. The reflection film **331** includes a metal material. Note that the reference numeral **332** denotes a filling member that fills an opening in the reflection film **331** on the circuit board **20** side. From the viewpoint of bondability to the circuit board **20**, the filling member **332** is formed by using the same material as the material of the planarization film **27**.

(173) The position of the light reflecting surface of the reflection film **331** is defined by the thickness of a layer included in the interlayer insulation film **330**. The film thickness of a layer included in the interlayer insulation film **330** and the film thickness of the organic layer **60** can be controlled with high precision by a film forming process. As a result, the dimension between each of the light reflecting surfaces of the reflection films **331A**, **331B**, and **331C** and the second electrode **70** (the portions indicated by arrows in FIG. 25) can be set with high precision.

(174) The first electrode **41** is connected to the drive circuit that drives the pixel **10** via the conductive portion **333** connected to the contact plug **28**.

(175) The foregoing has described a detailed structure of the display device **3**. The above-described display device **3** can be manufactured as follows.

(176) FIGS. 26 to 35 are schematic partial end views for explaining the method for manufacturing the display device according to the third embodiment.

(177) Step-300

(178) First, the circuit board **20** on which a drive circuit is formed is prepared. The configuration of the circuit board **20** is similar to the configuration described in [Step-100] above, and thus the description thereof is omitted.

(179) Subsequently, the interlayer insulation film **330** having the reflection film **331** formed therein is disposed on the circuit board **20** by the procedure illustrated in FIGS. 26 to 35.

(180) Step-310 (see FIG. 26A)

(181) The substrate **39** of a silicon wafer is prepared, and the interlayer insulation film **330** is formed thereon by, for example, stacking two types of layers alternately, such as a layer of silicon oxide and a layer of silicon nitride (see FIG. 26B). In the example shown in the figure, the first layer **330A**, the third layer **330C**, and the fifth layer **330E** are layers of silicon oxide, while the second layer **330B** and the fourth layer **330D** are layers of silicon nitride.

(182) Step-320 (see FIG. 26B)

(183) Then, in the interlayer insulation film **330**, an opening **OP331A** is formed in a portion corresponding to the reflection film **331A** such that the boundary plane between the first layer **330A** and the second layer **330B** is exposed to the bottom, an opening **OP331B** is formed in a portion corresponding to the reflection film **331B** such that the boundary plane between the second layer **330B** and the third layer **330C** is exposed to the bottom, and an opening **OP331C** is formed in a portion corresponding to the reflection film **331C** such that the boundary plane between the third layer **330C** and the fourth layer **330D** is exposed to the bottom.

(184) The opening **OP331A** can be formed by performing dry etching under the condition that the first layer **330A** acts as a stopper film, the opening **OP331B** can be formed by performing dry etching under the condition that the second layer **330B** acts as a stopper film, and the opening **OP331C** can be formed by performing dry etching under the condition that the third layer **330C** acts as a stopper film. Note that etching is only needed in a region in need of etching, and thus a portion not to be etched can be handled by, for example, forming a mask or the like on the portion as appropriate.

(185) Furthermore, at the same time, an opening **OP333** is formed in the interlayer insulation film **330** in a portion corresponding to the conductive portion **330** so as to penetrate through the interlayer insulation film **330**. The opening **OP333** can be formed by, for example, performing dry etching under the condition that the substrate **39** acts as a stopper.

(186) Step-330 (see FIG. 27)

(187) Then, the reflection film **331** and others are formed in the opening **OP331**, while the conductive portion **333** is formed in the opening **OP333**. For example, a silver thin film is formed on the entire surface including the opening by a sputtering method, and then the filling member **32** to fill the opening in the reflection film **331** is formed, followed by planarization carried out by using, for example, a CMP method.

(188) Step-340 (see FIGS. 28, 29, and 30)

(189) Subsequently, with the interlayer in film. **330** and the circuit board **20** facing each other (see FIG. 28), the interlayer insulation film **330** and the circuit board **20** are joined together. The surfaces of the interlayer insulation film **330** and the circuit board **20** are activated, and then the surface-activated substances are brought into close contact with each other, whereby the interlayer insulation film **330** and the circuit board **20** can be joined together by an atomic force (see FIG. 29). Then, the substrate **39** is removed (see FIG. 30).

(190) Next, the light emission unit **ELP** and others are formed on the interlayer insulation film **330** by the procedure illustrated in FIGS. 31 to 34.

(191) Step-350 (see FIG. 31)

(192) First, the first electrode **41** is formed on the interlayer insulation film **330**. The configuration of the first electrode **41** is similar to the configuration described in [Step-150] above, and thus the description thereof is omitted.

(193) Step-360 (see FIG. 32)

(194) Next, the partition **51** serving as an inlet-pixel insulation film is formed between the first electrode **41** and the first electrode **41**. The configuration of the partition **51** is similar to the configuration described in [Step-160] above, and thus the description thereof is omitted.

(195) Step-370 (see FIG. 33)

(196) Next, the organic layer **60** that emits white light is formed on the entire surface including the

first electrode **41** serving as an anode electrode by, for example, sequentially forming a hole injection layer, a hole transport layer, a red light emission layer, a light emission separation layer, a blue light emission layer, a green light emission layer, and an electron transport layer.

(197) Step-380 (see FIGS. **34** and **35**)

(198) Next, the second electrode **70** serving as a cathode electrode is formed on the entire surface of the organic layer **60**. The second electrode **70** can be obtained by, for example, forming a film of a silver-magnesium alloy on the entire surface by a vapor deposition method (see FIG. **34**). After that, the protection film **80** is formed on the entire surface, and then the counter substrate on which the color filter **90** is formed is stuck thereto, whereby the display device **3** illustrated in FIG. **25** can be obtained.

(199) A resonator structure is also formed in the display device **3** between the light reflecting surface of the reflection film **331** and the second electrode **70** (the portion indicated by an arrow in FIG. **35**). The distance in this portion is defined by the thicknesses of the organic layer **60**, the first electrode **41**, and each layer included in the interlayer insulation film **330**. These film thicknesses can be controlled with high precision due to the process of forming the components. Therefore, variations in luminous efficacy and emission color caused by variations in resonator structure can be suppressed.

(200) In addition, the light reflecting surface of the reflection film **331** is formed by embedding a metal material in the interlayer insulation film **330**. Therefore, the light reflecting surface is not exposed to the outside air. For this reason, a material that has a high reflectance but is prone to oxidization, such as silver or a silver alloy, can be used as a material for forming the reflection film **331** without trouble.

(201) Furthermore, a pixel, with a longer distance between the reflection film **331** and the first electrode **41** has more layer cycles in the interlayer insulation film **330**, and thus the pixel can reduce lateral escape of light. On the other hand, a pixel with a shorter distance between the reflection film **331** and the first electrode **41** is likely to provide higher efficiency because interfacial attenuation is suppressed. Therefore, for a color pixel having higher luminous efficacy, light loss due to lateral escape is reduced by increasing the number of stacked layers, and for a color pixel having lower luminous efficacy, color mixture is reduced by decreasing the number of stacked layers, thereby achieving optimum luminous efficacy of a plurality of light emission pixels as a whole.

(202) In each of various display devices according to the present disclosure described above, the first electrode is formed on the interlayer insulation film, and the reflection film, which is formed below the first electrode, is formed to have a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film. Furthermore, the first electrode, the organic layer, and the second electrode are stacked. Therefore, the positional relationship between the organic layer and the reflection film can be set with high precision by appropriately setting the thickness of the interlayer insulation film.

(203) Electronic Apparatus

(204) The display device of the present disclosure described above can be used as a display unit (display device) of an electronic apparatus in any field for displaying video signals input to the electronic apparatus or video signals generated in the electronic apparatus as an image or video. For example, the display device can be used as a display unit in a television set, a digital still camera, a notebook personal computer, a mobile terminal device such as a mobile phone, a video camera, a head-mounted display (a display attached on one's head), and so on.

(205) The display device of the present disclosure may even include a module-shaped device in a sealed configuration. An example may be a display module formed by attaching opposed units including transparent glass or the like to the pixel array unit. Note that the display module may be provided with a circuit unit, a flexible printed circuit (FPC), and the like for inputting and

outputting signals and the like from the outside to the pixel array unit. As specific examples of an electronic apparatus employing the display device of the present disclosure, a digital still camera and a head-mounted display are shown below. Note that, however, the specific examples illustrated here are not restrictive but are merely examples.

Specific Example 1

(206) FIG. **36** is an external view of a lens-interchangeable single-lens reflex type digital still camera; FIG. **36A** shows a front view thereof and FIG. **36B** shows a rear view thereof. The lens-interchangeable single-lens reflex type digital still camera includes, for example, an interchangeable photographing lens unit (interchangeable lens) **412** on the front right side of a camera main body (camera body) **411** and a grip portion **413** to be gripped by a photographer on the front left side.

(207) In addition, a monitor **414** is disposed substantially in the center of the rear surface of the camera main body **411**. A viewfinder (eyepiece window) **415** is disposed above the monitor **414**. By looking through the viewfinder **415**, the photographer can visually recognize the optical image of the subject guided from the photographing lens unit **412** to determine the composition.

(208) In the lens-interchangeable single-lens reflex type digital still camera as configured above, the display device of the present disclosure can be used as the viewfinder **415**. That is, the lens-interchangeable single-lens reflex type digital still camera according to the present example is produced by using the display device of the present disclosure as the viewfinder **415**.

Specific Example 2

(209) FIG. **37** is an external view of a head-mounted display. The head-mounted display includes, for example, an ear hook portion **512** on both sides of an eyeglass-shaped display portion **511** so that the head-mounted display is attached on the user's head. In the head-mounted display, the display device of the present disclosure can be used as the display portion **511**. That is, the head-mounted display according to the present example is produced by using the display device of the present disclosure as the display portion **511**.

Specific Example 3

(210) FIG. **38** is an external view of a see-through head-mounted display. The see-through head-mounted display **611** includes a main body **612**, an arm **613**, and a lens barrel **614**.

(211) The main body **612** is connected to the arm **613** and to eyeglasses **600**. Specifically, an end of the main body **612** with respect to the long side direction is connected to the arm **613**, and one of the side surfaces of the main body **612** is connected to the eyeglasses **600** via a connection member. Note that the main body **612** may be directly attached on the head of a human body.

(212) The main body **612** contains a control board for controlling operations of the see-through head-mounted display **611** and also contains a display unit. The arm **613** connects the main body **612** and the lens barrel **614** and supports the lens barrel **614**. Specifically, the arm **613** is coupled to an end of the main body **612** and to an end of the lens barrel **614** to fix the lens barrel **614**.

Furthermore, the arm **613** contains a signal line for exchanging data regarding an image provided by the main body **612** to the lens barrel **614**.

(213) The lens barrel **614** projects, through an eyepiece, the image light provided by the main body **612** via the arm **613** onto the eyes of the user wearing the see-through head-mounted display **611**. In the see-through head-mounted display **611**, the display device of the present disclosure can be used as the display unit in the main body **612**.

(214) Others

(215) Note that the technology of the present disclosure may have the following configurations.

(216) A1

(217) A display device in which more than one pixel is arranged in a two-dimensional matrix on a circuit board, the pixel including a light emission unit including a first electrode, an organic layer, and a second electrode that are stacked, in which

(218) the first electrode is disposed for each light emission unit, and a partition is formed between

the

(219) first electrode and an adjacent first electrode, the organic layer and the second electrode are stacked on an entire surface including the first electrode and the partition,

(220) the first electrode is formed on an interlayer insulation film, and

(221) a reflection film is formed below the first electrode, the reflection film including a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film.

(222) A2

(223) The display device according to [A1], in which

(224) the interlayer insulation film includes different types of a plurality of insulation materials stacked to be in contact with each other.

(225) A3

(226) The display device according to [A2], in which

(227) the interlayer insulation film includes at least two types of layers selected from a layer of silicon oxide, a layer of silicon nitride, and a layer of silicon oxynitride.

(228) A4

(229) The display device according to [A3], in which

(230) the interlayer insulation film is formed with two types of layers stacked alternately.

(231) A5

(232) The display device according to any one of [A2] to [A4], in which

(233) the number of layers in the interlayer insulation film located between the reflection film and the first electrode differs depending on a display color of the pixel.

(234) A6

(235) The display device according to any one of [A2] to [A5], in which

(236) a film thickness of the interlayer insulation film located between the reflection film and the first. electrode is set to be an optical distance in accordance with a display color of the pixel.

(237) A7

(238) The display device according to [A6], in which

(239) the optical distance satisfies a condition:

$$2L/\lambda + \Phi/2\pi = m$$
(m is an integer)

(240) where symbol Φ represents a phase shift of reflected light generated in the first electrode and the reflection film, symbol L represents the optical distance between the first electrode and the reflection film, and symbol λ represents a peak wavelength of a spectrum of light taken from the pixel.

(241) A8

(242) The display device according to any one of [A1] to [A7], in which

(243) the reflection film is embedded in an opening provided in the interlayer insulation film.

(244) A9

(245) The display device according to any one of [A1] to [A8], in which

(246) the reflection film includes a metal material.

(247) A10

(248) The display device according to [A9], in which.

(249) the reflection film includes silver or a silver alloy.

(250) A11

(251) The display device according to [A9], in which

(252) the reflection film includes an upper layer portion and a lower layer portion, the upper layer portion including silver or a silver alloy, and the lower layer portion including copper or a copper alloy.

(253) A12

(254) The display device according to any one of [A1] to [A11], in which

(255) the circuit board includes a drive circuit intended for driving the pixel, and

(256) the first electrode and the drive circuit are electrically connected.

(257) A13

(258) The display device according to [A12], in which

(259) the first electrode and the drive circuit are electrically connected via the reflection film.

(260) B1

(261) A method for manufacturing a display device in which more than one pixel is arranged in a two-dimensional matrix on a circuit board, the pixel including a light emission unit including a first electrode, an organic layer, and a second electrode that are stacked, the method including steps of: forming, on a substrate, an interlayer insulation film in which layers of different types of insulation materials are stacked to be in contact with each other; forming an opening in a region of the interlayer insulation film, the region corresponding to the first electrode, in such a way that a plane flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film is exposed to a bottom; embedding a reflection film in the opening; joining a surface of the embedded reflection film with the circuit board, and then removing the substrate; and forming, on the interlayer insulation film, a light emission unit including the first electrode, the organic layer, and the second electrode that are stacked.

B2

(262) The method for manufacturing the display device according to [B1], in which

(263) the interlayer insulation film includes different types of a plurality of insulation materials stacked to be in contact with each other.

(264) B3

(265) The method for manufacturing the display device according to [B2], in which

(266) the interlayer insulation film includes at least two types of layers selected from a layer of silicon oxide, a layer of silicon nitride, and a layer of silicon oxynitride.

(267) B4

(268) The method for manufacturing the display device according to [B3], in which

(269) the interlayer insulation film is formed with two types of layers stacked alternately.

(270) B5

(271) The method for manufacturing the display device according to any one of [B2] to [B4], in which

(272) the number of layers in the interlayer insulation film located between the reflection film and the first electrode differs depending on a display color of the pixel.

(273) B6

(274) The method for manufacturing the display device according to any one of [B2] to [B5], in which

(275) a film thickness of the interlayer insulation film located between the reflection film and the first electrode is set to be an optical distance in accordance with a display color of the pixel.

(276) B7

(277) The method for manufacturing the display device according to [B6], in which

(278) the optical distance L satisfies a condition:

$2L/\lambda + \Phi/2\pi = m$ (m is an integer)

(279) where symbol Φ represents a phase shift of reflected light generated in the first electrode and the reflection film, symbol L represents the optical distance between the first electrode and the reflection film, and symbol λ represents a peak wavelength of a spectrum of light taken from the pixel.

(280) B8

(281) The method for manufacturing the display device according to any one of [B1] to [B7], in which

(282) the reflection film is embedded in an opening provided in the interlayer insulation film.

- (283) B9
- (284) The method for manufacturing the display device according to any one of [B1] to [B8], in which
- (285) the reflection film includes a metal material.
- (286) B10
- (287) The method for manufacturing the display device according to [B9], in which
- (288) the reflection film includes silver or a silver alloy.
- (289) B11
- (290) The method for manufacturing the display device according to [B9], in which
- (291) the reflection film includes an upper layer portion and a lower layer portion, the upper layer portion including silver or a silver alloy, and the lower layer portion including copper or a copper alloy.
- (292) B12
- (293) The method for manufacturing the display device according to any one of [B1] to [B11], in which
- (294) the circuit board includes a drive circuit intended for driving the pixel, and
- (295) the first electrode and the drive circuit are electrically connected.
- (296) B13
- (297) The method for manufacturing the display device according to [B12], in which
- (298) the first electrode and the drive circuit are electrically connected via the reflection film.
- (299) C1
- (300) An electronic apparatus including a display device in which more than one pixel is arranged in a two-dimensional matrix on a circuit board, the pixel including a light emission unit including a first electrode, an organic layer, and a second electrode that are stacked, in which in the display device, the first electrode is disposed for each light emission unit, and a partition is formed between the first electrode and an adjacent first electrode, the organic layer and the second electrode are stacked on an entire surface including the first electrode and the partition, the first electrode is formed on an interlayer insulation film, and a reflection film is formed below the first electrode, the reflection film including a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film.
- C2
- (301) The electronic apparatus according to [C1], in which
- (302) the interlayer insulation film includes different types of a plurality of insulation materials stacked to be in contact with each other.
- (303) C3
- (304) The electronic apparatus according to [C2], in which
- (305) the interlayer insulation film includes at least two types of layers selected from a layer of silicon oxide, a layer of silicon nitride, and a layer of silicon oxynitride.
- (306) C4
- (307) The electronic apparatus according to [C3], in which
- (308) the interlayer insulation film is formed with two types of layers stacked alternately.
- (309) C5
- (310) The electronic apparatus according to any one of [C2] to [C4], in which
- (311) the number of layers in the interlayer insulation film located between the reflection film and the first electrode differs depending on a display color of the pixel.
- (312) C6
- (313) The electronic apparatus according to any one of [C2] to [C5], in which
- (314) a film thickness of the interlayer insulation film located between the reflection film and the first electrode is set to be an optical distance in accordance with a display color of the pixel.
- (315) C7

- (316) The electronic apparatus according to [C6], in which
 (317) the optical distance L satisfies a condition:
 $2L/\lambda + \Phi/2\pi = m$ (m is an integer)
 (318) where symbol Φ represents a phase shift of reflected light generated in the first electrode and the reflection film, symbol L represents the optical distance between the first electrode and the reflection film, and symbol λ represents a peak wavelength of a spectrum of light taken from the pixel.
 (319) C8
 (320) The electronic apparatus according to any one of [C1] to [C7], in which
 (321) the reflection film is embedded in an opening provided in the interlayer insulation film.
 (322) C9
 (323) The electronic apparatus according to any one of [C1] to [C8], in which
 (324) the reflection film includes a metal material.
 (325) C10
 (326) The electronic apparatus according to [C9], in which
 (327) the reflection film includes silver or a silver alloy.
 (328) C11
 (329) The electronic apparatus according to [C9], in which
 (330) the reflection film includes an upper layer portion and a lower layer portion, the upper layer portion including silver or a silver alloy, and the lower layer portion including copper or a copper alloy.
 (331) C12
 (332) The electronic apparatus according to any one of [C1] to [C11], in which the circuit board includes a drive circuit intended for driving the pixel, and the first electrode and the drive circuit are electrically connected.
 C13
 (333) The electronic apparatus according to [C12], in which
 (334) the first electrode and the drive circuit are electrically connected via the reflection film.

REFERENCE SIGNS LIST

(335) **1, 2, 3** Display device **10** Pixel **11** Display region **20, 220** Circuit board **21** Base material **22** Gate electrode **23** Gate insulation film **24** Semiconductor material layer **25** Planarization film **26** Source/drain electrode **27** Planarization film **28, 228** Contact plug **30, 330** Interlayer insulation film **30A** First layer **30B** Second layer **30C** Third layer **330A** First layer **330B** Second layer **330C** Third layer **320D** Fourth layer **330E** Fifth layer **31, 331, 331A, 331B, 331C** Reflection film **32, 232** Filling member **33, 333** Conductive portion **39** Substrate (silicon wafer) **41** First electrode **51** Partition **60** Organic layer **70** Second electrode **80** Protection film **90** Color filter **91** Light shielding region **92** Filter region **100** Power supply unit **101** Scanning unit **102** Data driver **411** Camera main body **412** Photographing lens unit **413** Grip portion **414** Monitor **415** Viewfinder **511** Eyeglass-shaped display portion **512** Ear hook portion **600** Eyeglasses (eyewear) **611** See-through head-mounted display **612** Main body **613** Arm **614** Lens barrel

Claims

1. A display device comprising: a plurality of pixels arranged in a two-dimensional matrix on a circuit board, one of the plurality of pixels including a light emission unit including a first electrode, an organic layer, and a second electrode that are stacked in a stacking direction, wherein the first electrode is disposed for the light emission unit, and a partition is formed between the first electrode and an adjacent first electrode, the organic layer and the second electrode are stacked on an entire surface including the first electrode and the partition, the first electrode is formed on an interlayer insulation film, and a reflection film is formed below the first electrode, the reflection

film comprising a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film; and a color filter layer including only a plurality of light shielding portions and a plurality of filter portions, one of the plurality of filter portions is interposed between and directly adjacent to two of the plurality of light shielding portions, wherein the one of the plurality of filter portions is over the one of the plurality of pixels in the stacking direction, wherein the color filter layer has a top surface that faces away from the plurality of pixels in the stacking direction, wherein one of the plurality of light shielding portions has a light shielding top surface, wherein one of the plurality of filter portions has a filter top surface, wherein a first portion of the top surface is formed by the light shielding top surface and a second portion of the top surface is formed by the filter top surface, wherein the color filter layer alternates between the plurality of light shielding portions and the plurality of filter portions, wherein the interlayer insulation film comprises three or more layers that are distinct and separate from each other, and wherein the interlayer insulation film comprises different types of a plurality of insulation materials that are stacked and in contact with each other and the reflection film.

2. The display device according to claim 1, wherein the interlayer insulation film comprises at least two types of layers selected from a layer of silicon oxide, a layer of silicon nitride, and a layer of silicon oxynitride.

3. The display device according to claim 1, wherein a number of layers in the interlayer insulation film located between the reflection film and the first electrode differs depending on a display color of the one of the plurality of pixels.

4. The display device according to claim 1, wherein a film thickness of the interlayer insulation film located between the reflection film and the first electrode is set to be an optical distance L in accordance with a display color of the one of the plurality of pixels.

5. The display device according to claim 4, wherein the optical distance L satisfies a condition: $2L/\lambda + \Phi/2\pi = m$ (m is an integer) where symbol Φ represents a phase shift of reflected light generated in the first electrode and the reflection film, symbol L represents the optical distance between the first electrode and the reflection film, and symbol λ represents a peak wavelength of a spectrum of light taken from the one of the plurality of pixels.

6. The display device according to claim 1, wherein the reflection film is embedded in an opening provided in the interlayer insulation film.

7. The display device according to claim 1, wherein the reflection film comprises a metal material.

8. The display device according to claim 7, wherein the reflection film comprises silver or a silver alloy.

9. The display device according to claim 7, wherein the reflection film comprises an upper layer portion and a lower layer portion, the upper layer portion including silver or a silver alloy, and the lower layer portion including copper or a copper alloy.

10. The display device according to claim 1, wherein the circuit board comprises a drive circuit intended for driving the one of the plurality of pixels, and the first electrode and the drive circuit are electrically connected.

11. The display device according to claim 10, wherein the first electrode and the drive circuit are electrically connected via the reflection film.

12. A display device comprising: a plurality of pixels arranged in a two-dimensional matrix on a circuit board, one of the plurality of pixels including a light emission unit including a first electrode, an organic layer, and a second electrode that are stacked in a stacking direction, wherein the first electrode is disposed for the light emission unit, and a partition is formed between the first electrode and an adjacent first electrode, the organic layer and the second electrode are stacked on an entire surface including the first electrode and the partition, the first electrode is formed on an interlayer insulation film, and a reflection film is formed below the first electrode, the reflection film comprising a light reflecting surface disposed to be flush with a boundary plane on which

different insulation materials are in contact with each other in the interlayer insulation film; and a color filter layer including only a plurality of light shielding portions and a plurality of filter portions, one of the plurality of filter portions is interposed between and directly adjacent to two of the plurality of light shielding portions, wherein the one of the plurality of filter portions is over the one of the plurality of pixels in the stacking direction, wherein the color filter layer has a top surface that faces away from the plurality of pixels in the stacking direction, wherein one of the plurality of light shielding portions has a light shielding top surface, wherein one of the plurality of filter portions has a filter top surface, wherein a first portion of the top surface is formed by the light shielding top surface and a second portion of the top surface is formed by the filter top surface, wherein the color filter layer alternates between the plurality of light shielding portions and the plurality of filter portions, the interlayer insulation film comprises three or more layers that are distinct and separate from each other wherein the three or more layers includes a first layer formed of a first material, a second layer formed of a second material, and a third layer formed of the first material, wherein the first layer is stacked on the second layer and the reflection film, and wherein the second layer is stacked on the third layer.

13. A method for manufacturing a display device in which a plurality of pixels is arranged in a two-dimensional matrix on a circuit board, the plurality of pixels including a pixel comprising a light emission unit including a first electrode, an organic layer, and a second electrode that are stacked, the method comprising steps of: forming, on a substrate, an interlayer insulation film in which layers of different types of insulation materials that are stacked and in contact with each other in a stacking direction; forming an opening in a region of the interlayer insulation film, the region corresponding to the first electrode, in such a way that a plane flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film is exposed to a bottom; embedding a reflection film in the opening; joining a surface of the embedded reflection film with the circuit board, and then removing the substrate; forming, on the interlayer insulation film, a light emission unit including the first electrode, the organic layer, and the second electrode that are stacked; forming, on the light emission unit, a planarization film; and forming, on the planarization film, a color filter layer including only a plurality of light shielding portions and a plurality of filter portions, one of the plurality of filter portions is interposed between and directly adjacent to two of the plurality of light shielding portions, wherein the one of the plurality of filter portions is over the one of the plurality of pixels in the stacking direction, wherein the color filter layer has a top surface that faces away from the plurality of pixels in the stacking direction, wherein one of the plurality of light shielding portions has a light shielding top surface, wherein one of the plurality of filter portions has a filter top surface, and wherein a first portion of the top surface is formed by the light shielding top surface and a second portion of the top surface is formed by the filter top surface, wherein the color filter layer alternates between the plurality of light shielding portions and the plurality of filter portions, wherein the interlayer insulation film comprises three or more layers that are distinct and separate from each other, and wherein the interlayer insulation film comprises different types of a plurality of insulation materials that are stacked and in contact with each other and the reflection film.

14. An electronic apparatus comprising: a display device including a plurality of pixels arranged in a two-dimensional matrix on a circuit board, one of the plurality of pixels including a light emission unit including a first electrode, an organic layer, and a second electrode that are stacked, wherein the first electrode is disposed for the light emission unit, and a partition is formed between the first electrode and an adjacent first electrode, the organic layer and the second electrode are stacked in a stacking direction on an entire surface including the first electrode and the partition, the first electrode is formed on an interlayer insulation film, and a reflection film is formed below the first electrode, the reflection film including a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film; and a color filter layer including only a plurality of light shielding

portions and a plurality of filter portions, one of the plurality of filter portions is interposed between and directly adjacent to two of the plurality of light shielding portions, wherein the one of the plurality of filter portions is over the one of the plurality of pixels in the stacking direction, wherein the color filter layer has a top surface that faces away from the plurality of pixels in the stacking direction, wherein one of the plurality of light shielding portions has a light shielding top surface, wherein one of the plurality of filter portions has a filter top surface, and wherein a first portion of the top surface is formed by the light shielding top surface and a second portion of the top surface is formed by the filter top surface, wherein the color filter layer alternates between the plurality of light shielding portions and the plurality of filter portions, wherein the interlayer insulation film comprises three or more layers that are distinct and separate from each other, and wherein the interlayer insulation film comprises different types of a plurality of insulation materials that are stacked and in contact with each other and the reflection film.

15. The electronic apparatus according to claim 14, wherein the interlayer insulation film comprises at least two types of layers selected from a layer of silicon oxide, a layer of silicon nitride, and a layer of silicon oxynitride.

16. The electronic apparatus according to claim 14, wherein a number of layers in the interlayer insulation film located between the reflection film and the first electrode differs depending on a display color of the one of the plurality of pixels.

17. The electronic apparatus according to claim 14, wherein a film thickness of the interlayer insulation film located between the reflection film and the first electrode is set to be an optical distance in accordance with a display color of the one of the plurality of pixels.

18. An electronic apparatus comprising: a display device including a plurality of pixels arranged in a two-dimensional matrix on a circuit board, one of the plurality of pixels including a light emission unit including a first electrode, an organic layer, and a second electrode that are stacked, wherein the first electrode is disposed for the light emission unit, and a partition is formed between the first electrode and an adjacent first electrode, the organic layer and the second electrode are stacked in a stacking direction on an entire surface including the first electrode and the partition, the first electrode is formed on an interlayer insulation film, and a reflection film is formed below the first electrode, the reflection film including a light reflecting surface disposed to be flush with a boundary plane on which different insulation materials are in contact with each other in the interlayer insulation film; and a color filter layer including only a plurality of light shielding portions and a plurality of filter portions, one of the plurality of filter portions is interposed between and directly adjacent to two of the plurality of light shielding portions, wherein the one of the plurality of filter portions is over the one of the plurality of pixels in the stacking direction, wherein the color filter layer has a top surface that faces away from the plurality of pixels in the stacking direction, wherein one of the plurality of light shielding portions has a light shielding top surface, wherein one of the plurality of filter portions has a filter top surface, and wherein a first portion of the top surface is formed by the light shielding top surface and a second portion of the top surface is formed by the filter top surface, wherein the color filter layer alternates between the plurality of light shielding portions and the plurality of filter portions, wherein the interlayer insulation film comprises three or more layers that are distinct and separate from each other wherein the three or more layers include a first layer formed of a first material, a second layer formed of a second material, and a third layer formed of the first material, wherein the first layer is stacked on the second layer and the reflection film, and wherein the second layer is stacked on the third layer.
