

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12412678
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Lee; Jung-Yong et al.

Fabrication method of conductive nanonetworks through adaptation of sacrificial layer

Abstract

There is provided a fabrication method of conductive nanonetworks through adaptation of a sacrificial layer includes: forming nanowire networks on a substrate; forming the sacrificial layer on a front surface of the substrate including the nanowire networks; removing the nanowire networks to expose a surface of the substrate within a region from which the nanowire networks are removed; forming a conductive material on the front surface of the substrate to fill the region, from which the nanowire networks are removed, with the conductive material while forming the conductive material on the sacrificial layer; and forming conductive nanonetworks made of the conductive material which fills the region from which the nanowire networks are removed, by removing the sacrificial layer.

Inventors: Lee; Jung-Yong (Daejeon, KR), Kim; Kyungmin (Daejeon, KR)

Applicant: KOREA ADVANCED INSTITUTE OF SCIENCE AND TECHNOLOGY
(Daejeon, KR)

Family ID: 81849444

Assignee: KOREA ADVANCED INSTITUTE OF SCIENCE AND TECHNOLOGY (South, KR)

Appl. No.: 17/539660

Filed: December 01, 2021

Prior Publication Data

Document Identifier	Publication Date
US 20220181047 A1	Jun. 09, 2022

Foreign Application Priority Data

KR	10-2020-0168463	Dec. 04, 2020
----	-----------------	---------------

Publication Classification

Int. Cl.: **H01B1/02** (20060101); **B82Y30/00** (20110101); **B82Y40/00** (20110101); **H01B1/22** (20060101); C23C14/04 (20060101); C23C16/04 (20060101); C23C30/00 (20060101); H01B13/00 (20060101); H10F71/00 (20250101); H10F77/20 (20250101)

U.S. Cl.:

CPC **H01B1/02** (20130101); **B82Y30/00** (20130101); **B82Y40/00** (20130101); **H01B1/22** (20130101); C23C14/042 (20130101); C23C16/042 (20130101); C23C30/00 (20130101); H01B13/0026 (20130101); H10F71/138 (20250101); H10F77/244 (20250101)

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
10831233	12/2019	Dodds et al.	N/A	N/A
2013/0203198	12/2012	Min	438/46	H10K 50/30
2016/0358747	12/2015	Zhu	N/A	C25D 5/48
2023/0183850	12/2022	Sheerin	427/540	C23C 14/20

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
1020060018466	12/2005	KR	N/A
1020090056038	12/2008	KR	N/A
1020090075957	12/2008	KR	N/A
101011447	12/2009	KR	N/A
1020130039017	12/2012	KR	N/A
1020130066724	12/2012	KR	N/A
101303988	12/2012	KR	N/A
1020150042634	12/2014	KR	N/A
1020170095054	12/2016	KR	N/A
1020180031179	12/2017	KR	N/A
101851641	12/2017	KR	N/A

OTHER PUBLICATIONS

Yang Jie et al: "High-Performance Transparent Conducting Metal Network Electrodes for Perovskite Photodetectors", Applied Materials & Interfaces, vol. 10, No. 2, Jan. 5, 2018 (Jan. 5, 2018), pp. 1996-2003, XP055833722, ISSN: 1944-8244, DOI: 10.1021/acsami.7b15205 (Year: 2018). cited by examiner

Korean Notice of Allowance in Korean Foreign Priority Application No. 10-2021-0151154, Aug. 14, 2024, 4 pages, with English translation. cited by applicant

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION

(1) This application claims priorities to Korean patent application No. 10-2020-0168463, filed on Dec. 4, 2020 and Korean patent application No 10-2021-0151154, filed on Nov. 5, 2021. The contents of the applications are incorporated herein by reference in their entirety.

BACKGROUND

1. Field

(2) The present disclosure relates to a fabrication method of conductive nanonetworks through the adaptation of a sacrificial layer, and more specifically, to a fabrication method of conductive nanonetworks through the adaptation of a sacrificial layer by which electrical properties and optical properties of the conductive nanonetworks can be improved by minimizing surface roughness and excluding contact resistance between nanowires in connecting a conductive material into a nanonetwork shape. [National R&D Program Which Supports This Invention] [Project Identification Number] 1711119623 [Project Number] 2020M3H4A1A02084906 [Ministry Name] Ministry of Science and ICT [Project Management (Specialized) Agency Name] National Research Foundation of Korea [Research Program Name] Source Technology Development of Future Nano-Material (R&D) [Research Project Title] Development of technology for optimizing high-efficient material and element for 100%-or-more-stretchable material-specific stretchable organic solar cell [Contribution Rate] 34/100 [Project Implementation Institute Name] Korea Advanced Institute of Science and Technology [Research Period] Jul. 1, 2020 to Dec. 31, 2020 [National R&D Program Which Supports This Invention] [Project Identification Number] 1711120360 [Project Number] 2020M3D1A2102869 [Ministry Name] Ministry of Science and ICT [Project Management (Specialized) Agency Name] National Research Foundation of Korea [Research Program Name] Future Material Discovery Support (R&D) [Research Project Title] Development of new high-performance material and element for electrochromic transparent display for vehicle [Contribution Rate] 33/100 [Project Implementation Institute Name] University of Seoul [Research Period] Jul. 23, 2020 to Jan. 22, 2021 [National R&D Program Which Supports This Invention] [Project Identification Number] 1711135134 [Project Number] 2020R1A4A1018516 [Ministry Name] Ministry of Science and ICT [Project Management (Specialized) Agency Name] National Research Foundation of Korea [Research Program Name] Group Research Support (R&D) [Research Project Title] Development of stretchable solar cell with consistent performance [Contribution Rate] 33/100 [Project Implementation Institute Name] Korea Advanced Institute of Science and Technology [Research Period] Jun. 1, 2021 to Feb. 28, 2022

2. Description of the Related Art

(3) Indium tin oxide (ITO) having properties of optical transmittance of about 85% and sheet resistance of 15 Ω /sq is widely used for nanoelectrodes of various display modules. However, limited reserves and mines of an indium component in ITO result in unstable supply and demand and a relatively high price thereof. In addition, an ITO deposition process has to be performed by expensive and large-sized vacuum equipment with high maintenance costs, and the oxide has a property of brittleness and thus is not suitable to be applied to a flexible electrode.

(4) Recently, research on a conductive nanofilm using flexible metal nanowires which can be produced through a low temperature process has been actively carried out. In other words, research on a conductive nanofilm which is fabricated into a mesh shape by using metal nanowires and is

used to function as a nanoelectrode of a flexible substrate or the like has been carried out.

Typically, a method of fabricating a mesh-shaped conductive nanofilm by randomly distributing metal nanowires through a solution process using a nanowire solution or the like is used.

(5) However, in a case of the conductive nanofilm using metal nanowires according to the related art, the conductive nanofilm is formed with metal nanowires being overlapped on one another, and thus the method in the related art has drawbacks of unavoidable contact resistance between metal nanowires and high surface roughness. In addition, a post-processing treatment such as a heat treatment or a laser treatment is required in order to reduce the contact resistance between metal nanowires, and the treatment is a process unsuitable for a flexible polymer substrate. Besides, the solution process according to the related art is difficult to apply to a very hydrophobic substrate.

SUMMARY

(6) The present disclosure is made to solve problems described above, and an object thereof is to provide a fabrication method of conductive nanonetworks through the adaptation of a sacrificial layer by which electrical properties and optical properties of the conductive nanonetworks can be improved by minimizing surface roughness and excluding contact resistance between nanowires in connecting a conductive material into a nanonetwork shape.

(7) In addition, another object of the present disclosure is to provide a fabrication method of conductive nanonetworks through the adaptation of a sacrificial layer by which a line width, density, and a height of the conductive nanonetworks can be controlled by adjusting a diameter and density of nanowire networks, a height of the sacrificial layer, and the like in a process of fabricating the conductive nanonetworks, and thereby electrical properties and optical properties of the conductive nanonetworks can be selectively adjusted.

(8) A fabrication method of conductive nanonetworks through adaptation of a sacrificial layer according to the invention to achieve the objects includes: forming nanowire networks on a substrate; forming the sacrificial layer on a front surface of the substrate including the nanowire networks; removing the nanowire networks to expose a surface of the substrate within a region from which the nanowire networks are removed; forming a conductive material on the front surface of the substrate to fill the region, from which the nanowire networks are removed, with the conductive material while forming the conductive material on the sacrificial layer; and removing the sacrificial layer to form conductive nanonetworks made of the conductive material which fills the region from which the nanowire networks are removed.

(9) A diameter and density of the nanowire networks and a height of the sacrificial layer may be adjustable. A line width, density, and a height of the conductive nanonetworks may be controllable through adjustment of the diameter and density of the nanowire networks and the height of the sacrificial layer.

(10) In the removing of the nanowire networks to expose the surface of the substrate within the region from which the nanowire networks are removed, the sacrificial layer present on the nanowire networks may be removed together with the nanowire networks, and the sacrificial layer present on the substrate may remain.

(11) In the removing of the nanowire networks to expose the surface of the substrate within the region from which the nanowire networks are removed, the nanowire networks and the sacrificial layer may have different dissolution selectivity from each other, and the sacrificial layer may remain on the substrate during the removing of the nanowire networks with a proper solvent.

(12) The nanowire networks may be formed through electrospinning.

(13) A diameter of the nanowire networks may be adjustable depending on a process condition of an electrospinning device. The diameter of the nanowire networks which are to be formed on the substrate may be adjustable by adjusting at least one of a diameter of a needle of the electrospinning device, a voltage applied to the needle, and a concentration of a solution containing a material which is used to form the nanowire networks. In addition, density of the nanowire networks may be adjustable by adjusting a process time of the electrospinning. Besides, the

diameter, a height, and surface roughness of the nanowire networks, bonding of the nanowire networks to the substrate, and the like may be adjustable using a post-processing treatment such as a heat treatment or evaporation solvent exposure after an electrospinning process.

(14) The substrate is any one of a flexible substrate, a semiconductor substrate, an insulation substrate, and an elastic substrate. In addition, the conductive material may be any one of conductive metal, a carbon-based conductive material, conductive polymer, and conductive nanoparticles, or a combination thereof.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) The above and other aspects, features and advantages of the disclosed example embodiments will be more apparent from the following detailed description taken in conjunction with the accompanying drawings in which:
- (2) FIG. 1 is a flowchart for illustrating a fabrication method of conductive nanonetworks through the adaptation of a sacrificial layer according to an embodiment of the invention;
- (3) FIG. 2 is a schematic view for illustrating the fabrication method of conductive nanonetworks through the adaptation of a sacrificial layer according to the embodiment of the invention;
- (4) FIGS. 3A to 3E are sectional views of a process for illustrating the fabrication method of conductive nanonetworks through the adaptation of a sacrificial layer according to the embodiment of the invention;
- (5) FIGS. 4A to 4C and 5A to 5D are photomicrographs and SEM pictures illustrating density of nanowire networks depending on a process time of electrospinning;
- (6) FIG. 6 illustrates a photomicrograph of a substrate on which PVP is formed;
- (7) FIGS. 7A to 7C illustrate SEM pictures of a substrate from which PMMA or PVP is removed;
- (8) FIG. 8 illustrates an AFM analysis result of the substrate from which PMMA or PVP is removed;
- (9) FIGS. 9 and 10 illustrate a photomicrograph and an SEM picture of a substrate on which conductive nanonetworks are formed by filling a region from which PMMA or PVP is removed, with Ag;
- (10) FIG. 11 illustrates an AFM analysis result of the substrate on which the conductive nanonetworks are formed;
- (11) FIGS. 12A to 12C are pictures illustrating states where conductive nanonetworks are formed on a glass substrate, a PET substrate, a thermoplastic polyurethane (TPU) substrate, respectively; and
- (12) FIG. 13 is an experimental result illustrating a property of optical transmittance of the substrate on which the conductive nanonetworks are formed.

DETAILED DESCRIPTION

(13) Example embodiments are described more fully hereinafter. The example embodiments may, however, be embodied in many different forms and should not be construed as limited to the example embodiments set forth herein. In the description, details of features and techniques may be omitted to more clearly disclose example embodiments.

(14) The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. As used herein, the singular forms “a,” “an” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. Furthermore, the use of the terms a, an, etc. do not denote a limitation of quantity, but rather denote the presence of at least one of the referenced item.

(15) Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art. It will be further

understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the present disclosure, and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein. All methods described herein can be performed in a suitable order unless otherwise indicated herein or otherwise clearly contradicted by context. The use of any and all examples, or exemplary language (e.g., “such as”), is intended merely to better illustrate the example embodiments and does not pose a limitation on the scope of the present disclosure unless otherwise claimed. No language in the specification should be construed as indicating any non-claimed element as essential to the practice of the present disclosure as used herein.

(16) The term “comprises” or “includes” as used herein throughout this specification, specifies presence of stated elements, but does not preclude presence or addition of one or more other elements unless the context clearly indicates otherwise.

(17) The present disclosure provides a technology of fabricating conductive nanonetworks through a new process.

(18) As described above in ‘Description of the Related Art’, a conductive nanofilm made of metal nanowires is provided to substitute for an ITO nanoelectrode of the related art, and the conductive metal-nanowire nanofilm is fabricated typically through a solution process using a nanowire solution. The solution process using a nanowire solution is a process of forming a conductive nanofilm having a configuration in which metal nanowires are connected to one another, by applying a solution containing dispersed metal nanowires on a substrate and removing a solvent. The conductive nanofilm made of metal nanowires can be fabricated through the process; however, the metal nanowires which are randomly dispersed in a solution are connected to one another in an overlapping manner. Hence, a finally fabricated conductive metal-nanowire nanofilm unavoidably has high surface roughness and contact resistance between nanowires, and it is not possible to adjust a height of the conductive metal-nanowire nanofilm.

(19) According to example embodiments of the present disclosure, the conductive nanonetworks are fabricated through adaptation of a sacrificial layer. In the fabrication method according to example embodiments of the present disclosure, the contact resistance between nanowires is excluded, and the surface roughness of the finally fabricated conductive nanonetworks is minimized. In addition, according to the fabrication method of example embodiments of the present disclosure, a line width, density, and a height of the conductive nanonetworks can be selectively adjusted, and thus the electrical properties and the optical properties of the conductive nanonetworks can be controlled. Here, the line width and density of the conductive nanonetworks can be adjusted by controlling a process condition of the nanowire networks, and a height of the conductive nanonetworks can be controlled by adjusting a height of the sacrificial layer.

(20) In the example embodiments of the present disclosure, the ‘conductive nanonetwork’ means that a conductive material forms a nanosized network. The ‘conductive nanonetwork’ in the example embodiments of the present disclosure corresponds to ‘forming a mesh shape by metal nanowires’ in the related art; however, the term ‘conductive nanonetwork’ is used in the example embodiments of the present disclosure to be differentiated from the related art using the metal nanowires and to emphasize a difference the example embodiments of the present disclosure and the related art. In the related art, connection between metal nanowires is induced by using a solution in which metal nanowires are dispersed in advance; on the other hand, in the example embodiments of the present disclosure, direct forming of the ‘nanosized network by the conductive material’ is performed without using metal nanowires, and thus the ‘conductive nanonetwork’ in the example embodiments of the present disclosure can be described to have a technical configuration different from that of ‘forming the mesh shape by metal nanowires’ in the related art.

(21) In the present disclosure, the conductive nanonetworks are fabricated through the adaptation of a sacrificial layer, and the present disclosure will be specifically described with an example embodiment, hereinafter. The fabrication method of conductive nanonetworks through the

adaptation of a sacrificial layer according to an example embodiment of the present disclosure is as follows.

(22) With reference to FIGS. 1 to 3E, first, a substrate **110** is prepared, and nanowire networks **120** are formed on the substrate **110** (S101, refer to (a) of FIG. 2 and FIG. 3A). Materials and types of substrate **110** are not limited. A semiconductor substrate **110** made of various materials can be used, an insulation substrate **110** such as a glass substrate **110** can be used, or a flexible polymer substrate **110** or an elastic substrate having elasticity can be used. Since an object of the present disclosure is to fabricate a nanoelectrode which can have a large area and can be used as the flexible substrate **110**, the following embodiment and experimental example will be described with the flexible substrate **110** as an example.

(23) In a state where the substrate **110**, for example, the flexible substrate **110**, is prepared, nanowire networks **120** are formed on the substrate **110**, and the nanowire networks **120** fulfills a function of defining a geometric shape of the conductive nanonetworks **150** in forming the conductive nanonetworks **150**. A location and a geometric shape of the nanowire networks **120** are virtually the same as those of the conductive nanonetworks **150**.

(24) The nanowire networks **120** having virtually the same geometric shape as that of the conductive nanonetworks **150** can be formed through electrospinning in the embodiment, and the process of forming the networks is not limited thereto. In a case of using the electrospinning process, the nanowire networks **120** can be formed through electrospinning of a solution onto the substrate **110**, the solution containing a material which forms the nanowire networks **120**. Various polymer materials can be used as the material that forms the nanowire networks **120**, and examples of the materials can include poly(methyl methacrylate) (PMMA) and poly(N-vinylpyrrolidone) (PVP). When PVP is used as the material of the nanowire networks **120**, water (H.sub.2O) can be used as a nanowire network dissolving solution, and thus various substrates such as a thermoplastic polyurethane substrate, which do not need to have oxidation resistance, can be used.

(25) In addition, when a material which forms the nanowire networks **120** is used, the material may need to have dissolution selectivity different from a material of a sacrificial layer **130**, and the dissolution selectivity will be described below. For reference, actual nanowire networks **120** form a chaotically structured nanowire shape; however, FIGS. 3A to 3E illustrate the nanowire networks **120** in a grid shape for convenience of description.

(26) In a case of forming the nanowire networks **120** on the flexible substrate **110** by using an electrospinning method, a diameter of the nanowire networks **120** can be adjusted by a process condition of the electrospinning. Specifically, an electrospinning device is configured to include a needle through which spinning of a solution is performed and a high-voltage generator that applies a voltage to the needle, and the diameter of the nanowire networks **120** which are to be formed on the substrate **110** can be adjusted by adjusting at least one of a diameter of the needle, the voltage applied to the needle, and a concentration of a solution containing a material which is used to form the nanowire networks **120**. As described above, the geometric shape of the nanowire networks **120** is virtually the same as that of the conductive nanonetworks **150**, and thus adjustment of the diameter of the nanowire networks **120** means adjustment of a line width of the conductive nanonetworks **150**.

(27) Hence, the diameter of the nanowire networks **120** can be adjusted by adjusting at least one of the diameter of the needle of the electrospinning device, the voltage applied to the needle, and the concentration of the solution containing the material which is used to form the nanowire networks **120**, and thus the line width of the conductive nanonetworks **150** can be controlled. In addition, the density of the nanowire networks **120** can be adjusted by adjusting a process time of the electrospinning, and thus the density of the conductive nanonetworks **150** can be selectively adjusted. FIGS. 4A to 4C and 5A to 5D are photomicrographs and SEM pictures illustrating density of the nanowire networks depending on a process time of electrospinning. Here, the density of the nanowire networks **120** or the density of the conductive nanonetworks **150** means density of the

nanowire networks or the conductive nanonetworks per unit area of the substrate.

(28) Since the line width and the density of the conductive nanonetworks **150** are directly associated with the electrical properties and the optical properties of the conductive nanonetworks **150**, the electrical properties and the optical properties of the conductive nanonetworks **150** can be eventually controlled by adjusting the diameter and the density of the nanowire networks **120**. On the other hand, a height of the conductive nanonetworks **150** can also be adjusted, and the height can be controlled by adjusting a height of the sacrificial layer **130** to be described below.

(29) In a state where the nanowire networks **120** are formed on the flexible substrate **110**, the sacrificial layer **130** is formed to have a uniform thickness on a front surface of the substrate **110** including the nanowire networks **120** (S102, refer to (b) of FIG. 2 and FIG. 3B). The material and the forming method of the sacrificial layer **130** are not limited, and physical vapor deposition (PVD), chemical vapor deposition (CVD), spin-coating, printing, or the like can be used as the forming method as an embodiment, and an organic material, an insulation film such as silicon oxide film, or the like can be used as the material of the sacrificial layer **130**. In an experimental example to be described below, fullerene is used as the material of the sacrificial layer **130**.

(30) In a state where the sacrificial layer **130** is formed on the front surface of the substrate **110** including the nanowire networks **120**, the nanowire networks **120** are selectively removed (S103, refer to (c) of FIG. 2 and FIG. 3C). As the nanowire networks **120** are removed, the sacrificial layer **130** formed on the nanowire networks **120** is also removed, and thus a surface of the substrate **110** within a region **120a**, from which the nanowire networks **120** are removed, is exposed.

(31) The nanowire networks **120** can be removed using a proper solvent. In other words, only the nanowire networks **120** can be selectively removed using the solvent, and the sacrificial layer **130** formed in contact with the substrate **110** is not removed. In order to selectively remove only the nanowire networks **120** without removing the sacrificial layer **130**, the material of the sacrificial layer **130** and the material of the nanowire networks **120** have to have different dissolution selectivity from each other. In an experimental example to be described below, PMMA and PVP are used as the respective materials of the nanowire networks **120**, and fullerene is used as the material of the sacrificial layer **130**. Acetone is used as the proper solvent of the nanowire networks in a case of using PMMA, and water (H.sub.2O) is used as the proper solvent of the nanowire networks in a case of using PVP.

(32) In a state where the surface of the substrate **110** within the region **120a** from which the nanowire networks **120** are removed by selectively removing the nanowire networks **120**, a conductive material **140** is formed on the front surface of the substrate **110** (S104, refer to (d) of FIG. 2 and FIG. 3D). Consequently, the conductive material **140** is formed on the sacrificial layer **130**, and the region **120a**, from which the nanowire networks **120** are removed, are filled with the conductive material **140**. The conductive material **140** which is used to fill the region **120a**, from which the nanowire networks **120** are removed, virtually means the conductive nanonetworks **150**.

(33) In the description provided above, the nanowire networks **120** are described to have virtually the same geometric shape as the conductive nanonetworks **150**. The region **120a**, from which the nanowire networks **120** are removed, is filled with the conductive material **140** such that the conductive nanonetworks **150** are formed, and thus it can be found that the nanowire networks **120** and the conductive nanonetworks **150** have the same geometric shape.

(34) The geometric shape of the nanowire networks **120** is virtually the same as that of the conductive nanonetworks **150**; however, the height of the conductive nanonetworks **150** can be adjusted to be different from the height of the nanowire networks **120**. Specifically, when the sacrificial layer **130** is formed to have a height higher than the height of the nanowire networks **120** during forming the sacrificial layer **130**, the height of the conductive nanonetworks **150** can be higher than the height of the nanowire networks **120**.

(35) On the other hand, various materials can be used as the conductive material **140** which forms the conductive nanonetworks **150**. Examples of the conductive material can include conductive

metal such as Ag, Au, Al, Cu, or Ga, a carbon-based conductive material such as graphene or CNT, conductive polymer, conductive nanoparticles, and the like, and a combination of these conductive materials **140**.

(36) In a state where the region **120a**, from which the nanowire networks **120** are removed, is filled with the conductive material **140** together with formation of the conductive material **140** on the sacrificial layer **130**, the sacrificial layer **130** is removed, and the fabrication method of conductive nanonetworks **150** through the adaptation of the sacrificial layer **130** according to the embodiment of the present disclosure is completed (S105, refer to (e) of FIG. 2 and FIG. 3E). As the sacrificial layer **130** is removed, the conductive material **140** on the sacrificial layer **130** is also removed, and only the conductive material **140** which is used to fill the region **120a**, from which the nanowire networks **120** are removed, is present on the substrate **110**. The conductive material **140** finally present on the substrate **110** forms networks having virtually the same shape as the nanowire networks **120** and is referred to as the conductive nanonetworks **150** in the present disclosure.

(37) As known from the fabrication method described above, a method of inducing connection between metal nanowires is used in the related art, whereas a method of forming the conductive nanonetworks by filling the region, from which the nanowire networks are removed, with the conductive material is used in the present disclosure. Hence, the ‘conductive nanonetworks’ of the present disclosure can be accepted as a technical configuration different from that of ‘forming the mesh shape with metal nanowires’ in the related art.

(38) In addition, the example embodiments of the present disclosure may be realized by the method of forming the conductive nanonetworks by filling the region, from which the nanowire networks are removed, with the conductive material and a configuration in which connection between metal nanowires is excluded, and thus the surface roughness of the conductive nanonetworks is more minimized, and the electrical properties and the optical properties are more improved than those in the related art. Besides, as described above, the line width, the density, and the height of the conductive nanonetworks can be adjusted by adjusting the diameter and the density of the nanowire networks and the height of the sacrificial layer, and thus the electrical properties and the optical properties of the conductive nanonetworks can be selectively controlled.

(39) The fabrication method of conductive nanonetworks through the adaptation of a sacrificial layer according to the example embodiments of the present disclosure is described as above. Hereinafter, the example embodiments of the present disclosure will be more specifically described with experimental examples.

Experimental Example: Fabrication and Property Analysis of Conductive Nanonetworks

(40) Electrospinning of poly(methyl methacrylate) (PMMA) is performed on a thermoplastic polyurethane substrate. Next, C60 fullerene is deposited through sputtering to have a thickness of 70 nm to 450 nm on the substrate. Then, PMMA is removed using acetone. Subsequently, Ag is deposited to have a thickness of 20 nm to 100 nm on a front surface of the substrate, and C60 fullerene is removed such that conductive nanonetworks made of Ag is completed.

(41) In addition, electrospinning of poly(N-vinylpyrrolidone) (PVP) is performed on a thermoplastic polyurethane substrate. Next, C60 fullerene is deposited through sputtering to have a thickness of 70 nm to 450 nm on the substrate. Then, PVP was removed using water (H.sub.2O). Subsequently, Ag is deposited to have a thickness of 20 nm to 100 nm on a front surface of the substrate, and C60 fullerene is removed such that conductive nanonetworks made of Ag was completed.

(42) FIGS. 4A to 4C and 6 illustrate photomicrographs of the substrates on which PMMA and PVP are formed, respectively. FIGS. 7A to 7C illustrate SEM pictures of the substrates from which PMMA or PVP is removed. With reference to FIGS. 4A to 4C and 6, electrospun PMMA and PVP can be observed to form nanosized network shapes. With reference to FIGS. 7A to 7C, a region of the substrate which is exposed by removing PMMA or PVP can be observed to match a region in which PMMA or PVP was present. Such results described above are also verified from atomic

force microscopy (AFM) analysis results illustrated in FIG. 8.

(43) FIGS. 9 and 10 illustrate a photomicrograph and an SEM picture of a substrate on which conductive nanonetworks are formed by filling a region, from which PMMA or PVP is removed, with Ag, and the conductive nanonetworks can be observed to be formed into the same shape as the shape of the nanowire networks. Such results described above are also verified from AFM analysis results illustrated in FIG. 11.

(44) FIGS. 12A to 12C are pictures illustrating states where conductive nanonetworks (Ag, liquid metal) are formed on a glass substrate, a PET substrate, a thermoplastic polyurethane (TPU) substrate, respectively, and the conductive nanonetworks can be observed to be present in a transparent state. In addition, sheet resistance is measured both in a state where the Ag conductive nanonetworks are formed on the glass substrate and in a state where the Ag conductive nanonetworks are formed on the PET substrate. The sheet resistance of 100 Ω /sq and 120 Ω /sq is measured to indicate that the Ag conductive nanonetworks have a good sheet resistance property.

(45) On the other hand, as a result of measuring through UV-vis the optical transmittance of the substrate on which the conductive nanonetworks are formed, the optical transmittance of about 85% or higher can be observed in the visible light wavelength range (400 nm to 700 nm) as illustrated in FIG. 13.

(46) The fabrication method of conductive nanonetworks through adaptation of a sacrificial layer according to the example embodiments of the present disclosure has the following effects.

(47) Since the nanowire networks and the sacrificial layer which define a geometric shape of the conductive nanonetworks are used, the line width, the density, and the height of the conductive nanonetworks may be selectively adjusted, and thus the electrical properties and the optical properties of the conductive nanonetworks may be controlled.

(48) In addition, a connection method of metal nanowires of the related art is excluded, and thus properties of surface roughness and electric resistance of the conductive nanonetworks can be improved.

(49) Besides, since a post-processing process such as a heat treatment or a laser treatment which is performed to improve electric resistance properties does not need to be performed, a flexible substrate may be used without limit, and a conductive nanonetwork process may be applied regardless of properties of a substrate.

(50) Additionally, since the conductive nanonetworks can be formed without applying a semiconductor process such as chemical vapor deposition, photolithography, or an etching process, a nanoelectrode having a large area may be easily fabricated.

(51) While the present disclosure has been described with respect to the specific embodiments, it will be apparent to those skilled in the art that various changes and modifications may be made without departing from the spirit and scope of the invention as defined in the following claims.

Claims

1. A fabrication method of conductive nanonetworks through adaptation of a sacrificial layer, comprising: electrospinning nanowire networks on a surface of a substrate to form the nanowire networks in contact with the surface of the substrate; depositing a sacrificial layer on the substrate including the nanowire networks to form the sacrificial layer in contact with the nanowire networks on the surface of the substrate and in contact with the surface of the substrate on which the nanowire networks are not formed; removing the nanowire networks with a solvent to expose a region of the surface of the substrate in contact with the nanowire networks, wherein the sacrificial layer formed in contact with the nanowire networks is removed together with the nanowire networks, and the sacrificial layer formed in contact with the surface of the substrate is not removed and remains; depositing a conductive material on the substrate including the sacrificial layer to fill a region of the surface of the substrate where the nanowire networks are removed; and

removing the sacrificial layer formed in contact with the surface of the substrate to expose a region of the surface of the substrate in contact with the sacrificial layer and to form conductive nanonetworks made of the conductive material which fills the region of the surface of the substrate where the nanowire networks are removed, wherein the conductive material formed on the sacrificial layer is removed together with the sacrificial layer, wherein the nanowire networks is poly (methyl methacrylate) (PMMA) or poly (N-vinylpyrrolidone) (PVP), wherein the material of the sacrificial layer is C60 fullerene, wherein the nanowire networks and the sacrificial layer have different dissolution selectivity from each other, and the sacrificial layer formed in contact with the surface of the substrate is not removed and remains during the removing of the nanowire networks with the solvent, wherein the solvent is acetone when using the PMMA as the nanowire networks and the solvent is water when using the PVP as the nanowire networks, and wherein a location and a geometric shape of the nanowire networks are the same as those of the conductive nanonetworks.

2. The fabrication method of conductive nanonetworks through adaptation of a sacrificial layer according to claim 1, further comprising: adjusting a diameter and density of the nanowire networks and a height of the sacrificial layer, and wherein a line width, density, and a height of the conductive nanonetworks are controllable through the step of adjusting of the diameter and density of the nanowire networks and the height of the sacrificial layer.
3. The fabrication method of conductive nanonetworks through adaptation of a sacrificial layer according to claim 1, further comprising: adjusting a diameter of the nanowire networks, wherein the diameter is adjusted by adjusting a process condition of an electrospinning device, and wherein the process condition of an electrospinning device is at least one of a diameter of a needle of the electrospinning device, a voltage applied to the needle, and a concentration of a solution containing a material which is used to form the nanowire networks.
4. The fabrication method of conductive nanonetworks through adaptation of a sacrificial layer according to claim 1, further comprising: adjusting density of the nanowire networks is adjustable by adjusting a process time of the electrospinning.
5. The fabrication method of conductive nanonetworks through adaptation of a sacrificial layer according to claim 1, wherein the substrate is at least one selected from a group comprising of a flexible substrate, a semiconductor substrate, an insulation substrate, and an elastic substrate.
6. The fabrication method of conductive nanonetworks through adaptation of a sacrificial layer according to claim 1, wherein the conductive material is at least one selected from a group comprising of conductive metal, carbon-based conductive material, conductive polymer, and conductive nanoparticles.
