

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12412860
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Chen; Hsien-Wei et al.

Package structure

Abstract

A package structure including a device die structure, an insulating encapsulant, and a first redistribution circuit is provided. The device die structure includes a first semiconductor die and a second semiconductor die. The first semiconductor die is stacked over and electrically connected to the second semiconductor die. The insulating encapsulant laterally encapsulates the device die structure. The insulating encapsulant includes a first encapsulation portion and a second encapsulation portion connected to the first encapsulation portion. The first encapsulation portion is disposed on the second semiconductor die and laterally encapsulates the first semiconductor die. The second encapsulation portion laterally encapsulates the first insulating encapsulation and the second semiconductor die. The first redistribution circuit structure is disposed on the device die and a first surface of the insulating encapsulant, and the first redistribution circuit structure is electrically connected to the device die.

Inventors:	Chen; Hsien-Wei (Hsinchu, TW), Chen; Ming-Fa (Taichung, TW)
Applicant:	Taiwan Semiconductor Manufacturing Co., Ltd. (Hsinchu, TW)
Family ID:	81367937
Assignee:	Taiwan Semiconductor Manufacturing Co., Ltd. (Hsinchu, TW)
Appl. No.:	18/359024
Filed:	July 26, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230369273 A1	Nov. 16, 2023

Related U.S. Application Data

continuation parent-doc US 17325649 20210520 US 11810883 child-doc US 18359024

Publication Classification

Int. Cl.: **H01L23/00** (20060101); **H01L23/31** (20060101); **H01L23/48** (20060101); **H01L23/538** (20060101); **H01L25/00** (20060101); **H01L25/065** (20230101); **H01L25/10** (20060101)

U.S. Cl.:

CPC **H01L24/24** (20130101); **H01L23/3135** (20130101); **H01L23/481** (20130101); **H01L24/25** (20130101); **H01L25/0652** (20130101); **H01L25/0657** (20130101); **H01L25/105** (20130101); **H01L25/50** (20130101); H01L23/5385 (20130101); H01L24/08 (20130101); H01L24/16 (20130101); H01L24/32 (20130101); H01L24/73 (20130101); H01L2224/08145 (20130101); H01L2224/16145 (20130101); H01L2224/24011 (20130101); H01L2224/2402 (20130101); H01L2224/24101 (20130101); H01L2224/24175 (20130101); H01L2224/25171 (20130101); H01L2224/32145 (20130101); H01L2224/73204 (20130101); H01L2224/73259 (20130101); H01L2224/73267 (20130101); H01L2225/06568 (20130101); H01L2225/1035 (20130101); H01L2225/1041 (20130101); H01L2225/1058 (20130101)

Field of Classification Search

CPC: H01L (24/24); H01L (24/08); H01L (24/16); H01L (24/32); H01L (24/73); H01L (23/3135); H01L (23/481); H01L (25/0657); H01L (21/4857); H01L (21/561); H01L (2924/181); H01L (2224/08145); H01L (2224/16145); H01L (2224/24011); H01L (2224/2402); H01L (2224/24101); H01L (2224/24175); H01L (2224/32145); H01L (2224/73204); H01L (2224/25171); H01L (2224/73259); H01L (2224/73267); H01L (2224/48091); H01L (2225/06568)

USPC: 257/621; 257/777

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
10032722	12/2017	Yu et al.	N/A	N/A
2017/0207197	12/2016	Yu et al.	N/A	N/A
2017/0345761	12/2016	Yu et al.	N/A	N/A
2020/0006309	12/2019	Chen et al.	N/A	N/A
2020/0279793	12/2019	Xie et al.	N/A	N/A
2020/0303343	12/2019	Manipatruni et al.	N/A	N/A
2020/0357770	12/2019	Chiang et al.	N/A	N/A
2020/0365557	12/2019	Tsai et al.	N/A	N/A
2021/0066254	12/2020	Yu	N/A	H01L 24/19
2021/0375826	12/2020	Chen	N/A	H01L 29/0657

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
20200002629	12/2019	KR	N/A
20200037051	12/2019	KR	N/A

Primary Examiner: Clark; Jasmine J

Attorney, Agent or Firm: Slater Matsil, LLP

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION (1) This application is a continuation of U.S. patent application Ser. No. 17/325,649, filed on May 20, 2021, now U.S. Pat. No. 11,810,883, issued Nov. 7, 2023, which claims priority to U.S. Provisional Application No. 63/136,744, filed on Jan. 13, 2021, each is hereby incorporated by reference herein in its entirety.

BACKGROUND

- (1) Semiconductor devices are used in a variety of electronic applications, such as personal computers, cell phones, digital cameras, and other electronic equipment, as examples. Semiconductor devices are typically fabricated by sequentially depositing insulating or dielectric layers, conductive layers, and semiconductive layers of material over a semiconductor substrate, and patterning the various material layers using lithography to form circuit components and elements thereon. Dozens or hundreds of integrated circuits are typically manufactured on a single semiconductor wafer. The individual dies are singulated by sawing the integrated circuits along a scribe line. The individual dies are then packaged separately, in multi-chip modules, or in other types of packaging, for example.
- (2) The semiconductor industry continues to improve the integration density of various electronic components (e.g., transistors, diodes, resistors, capacitors, etc.) by continual reductions in minimum feature size, which allow more components to be integrated into a given area.
-

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.
- (2) FIGS. 1A through 1D are cross-sectional views schematically illustrating a process flow for fabricating System on Integrated Circuits (SoICs) structures in accordance with some embodiments of the present disclosure.
- (3) FIGS. 2A through 2N are cross-sectional views schematically illustrating a process flow for fabricating integrated fan-out package structures of SoIC structures in accordance with some embodiments of the present disclosure.
- (4) FIGS. 3A through 3N are cross-sectional views schematically illustrating a process flow for fabricating integrated fan-out package structures in accordance with some other embodiments of the present disclosure.
- (5) FIGS. 4A through 4N are cross-sectional views schematically illustrating a process flow for fabricating integrated fan-out package structures in accordance with some alternative embodiments of the present disclosure.

DETAILED DESCRIPTION

- (6) The following disclosure provides many different embodiments, or examples, for implementing

different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(7) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(8) Other features and processes may also be included. For example, testing structures may be included to aid in the verification testing of the 3D packaging or 3DIC devices. The testing structures may include, for example, test pads formed in a redistribution layer or on a substrate that allows the testing of the 3D packaging or 3DIC, the use of probes and/or probe cards, and the like. The verification testing may be performed on intermediate structures as well as the final structure. Additionally, the structures and methods disclosed herein may be used in conjunction with testing methodologies that incorporate intermediate verification of known good dies to increase the yield and decrease costs.

(9) Packages and the methods of forming the same are provided in accordance with various exemplary embodiments. The intermediate stages of forming the packages are illustrated. The variations of the embodiments are discussed. Throughout the various views and illustrative embodiments, like reference numbers are used to designate like elements.

(10) FIGS. 1A through 1D are cross-sectional views schematically illustrating a process flow for fabricating System on Integrated Circuit (SoIC) structures in accordance with some embodiments of the present disclosure.

(11) Referring to FIG. 1A, a wafer **10** including semiconductor dies is provided. The semiconductor dies may be logic dies, System-on-Chip (SoC) dies or other suitable semiconductor dies. The wafer **10** may include a substrate **12** (e.g., a semiconductor substrate), through substrate vias (TSV) **14** embedded in the substrate **12**, an interconnect structure **16** disposed on the substrate **12**, and a bonding structure **18** disposed on the interconnect structure **16**, wherein the through substrate vias **14** are electrically connected to the interconnect structure **16**. The substrate **12** of the semiconductor wafer **10** may include a crystalline silicon wafer. The substrate **12** may include various doped regions depending on design requirements (e.g., p-type substrate or n-type substrate). In some embodiments, the doped regions may be doped with p-type or n-type dopants. The doped regions may be doped with p-type dopants, such as boron or BF₃; n-type dopants, such as phosphorus or arsenic; and/or combinations thereof. The doped regions may be configured for n-type Fin-type Field Effect Transistors (FinFETs) and/or p-type FinFETs. In some alternative embodiments, the substrate **12** may be made of some other suitable elemental semiconductor, such as diamond or germanium; a suitable compound semiconductor, such as gallium arsenide, silicon carbide, indium arsenide, or indium phosphide; or a suitable alloy semiconductor, such as silicon germanium carbide, gallium arsenic phosphide, or gallium indium phosphide.

(12) The through substrate vias **14** may be formed by forming recesses in the substrate **12** by, for example, etching, milling, laser techniques, a combination thereof, and/or the like. A thin barrier

layer may be conformally deposited over the front side of the substrate **12** and in the openings, such as by chemical vapor deposition (CVD), atomic layer deposition (ALD), physical vapor deposition (PVD), thermal oxidation, a combination thereof, and/or the like. The barrier layer may comprise a nitride or an oxynitride, such as titanium nitride, titanium oxynitride, tantalum nitride, tantalum oxynitride, tungsten nitride, a combination thereof, and/or the like. A conductive material is deposited over the thin barrier layer and in the openings. The conductive material may be formed by an electro-chemical plating process, CVD, ALD, PVD, a combination thereof, and/or the like. Examples of conductive materials are copper, tungsten, aluminum, silver, gold, a combination thereof, and/or the like. Excess conductive material and barrier layer may be removed from the front side of the substrate **12** by, for example, chemical mechanical polishing. Thus, in some embodiments, the through substrate vias **14** may comprise a conductive material and a thin barrier layer between the conductive material and the substrate **12**.

(13) The interconnect structure **16** may include one or more dielectric layers (for example, one or more interlayer dielectric (ILD) layers, intermetal dielectric (IMD) layers, or the like) and interconnect wirings embedded in the one or more dielectric layers, and the interconnect wirings are electrically connected to the semiconductor devices (e.g., FinFETs) formed in the substrate **12** and/or the through substrate vias **14**. The material of the one or more dielectric layers may include silicon oxide (SiO.sub.x , where $x > 0$), silicon nitride (SiN.sub.x , where $x > 0$), silicon oxynitride (SiO.sub.xN.sub.y , where $x > 0$ and $y > 0$) or other suitable dielectric material. The interconnect wirings may include metallic wirings. For example, the interconnect wirings include copper wirings, copper pads, aluminum pads or combinations thereof. In some embodiments, the through substrate vias **14** may extend through one or more layers of the interconnect structure **16** and into the substrate **12**.

(14) The bonding structure **18** may include a bonding dielectric layer **18a** and bonding conductors **18b** embedded in the bonding dielectric layer **18a**. The material of the bonding dielectric layer **18a** may be silicon oxide (SiO.sub.x , where $x > 0$), silicon nitride (SiN.sub.x , where $x > 0$), silicon oxynitride (SiO.sub.xN.sub.y , where $x > 0$ and $y > 0$) or other suitable dielectric material, and the bonding conductors **18b** may be conductive vias (e.g., copper vias), conductive pads (e.g., copper pads) or combinations thereof. The bonding structure **18** may be formed by depositing a dielectric material through a chemical vapor deposition (CVD) process (e.g., a plasma enhanced CVD process or other suitable process); patterning the dielectric material to form the bonding dielectric layer **18a** including openings or through holes; and filling conductive material in the openings or through holes defined in the bonding dielectric layer **18a** to form the bonding conductors **18b** embedded in the bonding dielectric layer **18a**.

(15) Referring to FIG. **1A** and FIG. **1B**, the semiconductor wafer **10** is singulated by a wafer sawing process performed along scribe lines **SL1** such that singulated semiconductor dies **20** are obtained. Each of the singulated semiconductor dies **20** may include a substrate **12**, through substrate vias **14** embedded in the substrate **12**, an interconnect structure **16** disposed on the substrate **12**, and a bonding structure **18** disposed on the interconnect structure **16**. As illustrated in FIG. **1B**, the through substrate vias **14** are buried in the substrate **12** and the interconnect structure **16**. The through substrate vias **14** are not revealed from a back surface of the substrate **12** at this stage.

(16) Referring to FIG. **1C**, a semiconductor wafer **11** including semiconductor dies is provided. The semiconductor dies may be logic dies, System-on-Chip (SoC) dies or other suitable semiconductor dies. The semiconductor dies **20** and the semiconductor dies in the semiconductor wafer **11** may perform the same function or different functions. In some embodiments, the semiconductor dies **20** and the semiconductor dies in the semiconductor wafer **11** are System on Chip (SoC) dies. The semiconductor wafer **11** may include a substrate **13** (e.g., a semiconductor substrate), an interconnect structure **15** disposed on the substrate **13**, and a bonding structure **17** disposed on the interconnect structure **15**. In some embodiments, a die-attachment film **19** is attached to a back

surface of the semiconductor wafer **11**. The substrate **13** of the semiconductor wafer **11** may include a crystalline silicon wafer. The substrate **13** may include various doped regions depending on design requirements (e.g., p-type substrate or n-type substrate). In some embodiments, the doped regions may be doped with p-type or n-type dopants. The doped regions may be doped with p-type dopants, such as boron or BF₂; n-type dopants, such as phosphorus or arsenic; and/or combinations thereof. The doped regions may be configured for n-type Fin-type Field Effect Transistors (FinFETs) and/or p-type FinFETs. In some alternative embodiments, the substrate **13** may be made of some other suitable elemental semiconductor, such as diamond or germanium; a suitable compound semiconductor, such as gallium arsenide, silicon carbide, indium arsenide, or indium phosphide; or a suitable alloy semiconductor, such as silicon germanium carbide, gallium arsenic phosphide, or gallium indium phosphide.

(17) The interconnect structure **15** may include one or more dielectric layers (for example, one or more interlayer dielectric (ILD) layers, intermetal dielectric (IMD) layers, or the like) and interconnect wirings embedded in the one or more dielectric layers, and the interconnect wirings are electrically connected to the semiconductor devices (e.g., FinFETs) formed in the substrate **12**. The material of the one or more dielectric layers may include silicon oxide (SiO_x, where $x > 0$), silicon nitride (SiN_x, where $x > 0$), silicon oxynitride (SiO_xN_y, where $x > 0$ and $y > 0$) or other suitable dielectric material. The interconnect wirings may include metallic wirings. For example, the interconnect wirings include copper wirings, copper pads, aluminum pads or combinations thereof.

(18) The bonding structure **17** may include a bonding dielectric layer **17a** and bonding conductors **17b** embedded in the bonding dielectric layer **17a**. The material of the bonding dielectric layer **17a** may be silicon oxide (SiO_x, where $x > 0$), silicon nitride (SiN_x, where $x > 0$), silicon oxynitride (SiO_xN_y, where $x > 0$ and $y > 0$) or other suitable dielectric material, and the bonding conductors **17b** may be conductive vias (e.g., copper vias), conductive pads (e.g., copper pads) or combinations thereof. The bonding structure **17** may be formed by depositing a dielectric material through a chemical vapor deposition (CVD) process (e.g., a plasma enhanced CVD process or other suitable process); patterning the dielectric material to form the bonding dielectric layer **17a** including openings or through holes; and filling conductive material in the openings or through holes defined in the bonding dielectric layer **17a** to form the bonding conductors **17b** embedded in the bonding dielectric layer **17a**.

(19) The singulated semiconductor dies **20** are picked-up, placed on and bonded to the semiconductor wafer **11** through a chip-to-wafer bonding process such that the bonding structures **18** of the singulated semiconductor dies **20** are in contact with the bonding structure **17** of the semiconductor wafer **11**. A bonding process is performed to bond the bonding structures **18** of the singulated semiconductor dies **20** with the bonding structure **17** of the semiconductor wafer **11**. The bonding process may be a hybrid bonding process that includes dielectric-to-dielectric bonding and metal-to-metal bonding. After performing the above-mentioned bonding process, a dielectric-to-dielectric bonding interface is formed between the bonding dielectric layer **18a** and the bonding dielectric layer **17a**, and metal-to-metal bonding interfaces are formed between the bonding conductors **18c** and bonding conductors **17b**.

(20) Referring to FIG. 1C and FIG. 1D, the semiconductor wafer **11** and the die-attachment film **19** are singulated by a wafer sawing process performed along scribe lines SL2 such that multiple singulated device dies or SoIC dies **22** are obtained. Each of the singulated SoIC dies **22** may include a singulated semiconductor die **21** and a singulated semiconductor die **20** stacked over the singulated semiconductor die **21**, wherein the singulated semiconductor die **20** and the singulated semiconductor die **21** are bonded in a face-to-face manner. As illustrated in FIG. 1D, in each of the singulated SoIC dies **22**, portions of the bonding dielectric layer **17a** of the singulated semiconductor die **21** are exposed. The lateral dimension (e.g., width and/or length) of the singulated semiconductor die **21** may be greater than the lateral dimension (e.g., width and/or

length) of the singulated semiconductor die **20**.

(21) FIGS. 2A through 2N are cross-sectional views schematically illustrating a process flow for fabricating integrated fan-out (InFO) package structures of SoIC dies in accordance with some embodiments of the present disclosure. FIGS. 2A through 2N illustrate the packaging process of the SoIC dies **22** shown in FIG. 1D to form InFO package structures, so that the overlying electrical connectors (such as solder regions) may be distributed to regions larger than the SoIC dies **22**.

(22) Referring to FIG. 2A, a carrier **60** including a de-bonding layer **62** formed thereon is provided. In some embodiments, the carrier **60** is a glass substrate, a ceramic carrier, or the like. The carrier **60** may have a round top-view shape and a size of a silicon wafer. For example, carrier **60** may have an 8-inch diameter, a 12-inch diameter, or the like. The de-bonding layer **62** may be formed of a polymer-based material (e.g., a Light To Heat Conversion (LTHC) material), which may be subsequently removed along with the carrier **60** from the overlying structures that will be formed in subsequent steps. In some embodiments, the de-bonding layer **62** is formed of an epoxy-based thermal-release material. In other embodiments, the de-bonding layer **62** is formed of an ultra-violet (UV) glue. The de-bonding layer **62** may be dispensed as a liquid and cured. In alternative embodiments, the de-bonding layer **62** is a laminate film and is laminated onto the carrier **60**. The top surface of the de-bonding layer **62** is substantially planar.

(23) Referring to FIGS. 2A through 2C, a redistribution circuit structure **61** including a dielectric layer **64**, redistribution wirings **66** and a dielectric layer **68** is formed on the de-bonding layer **62** such that the de-bonding layer **62** is between the carrier **60** and the dielectric layer **64** of the redistribution circuit structure **61**. As shown in FIG. 2A, the dielectric layer **64** is formed on the de-bonding layer **62**. In some embodiments, the dielectric layer **64** is formed of a polymer, which may also be a photo-sensitive material such as polybenzoxazole (PBO), polyimide, benzocyclobutene (BCB), or the like, which may be easily patterned using a photolithography process. In some embodiments, the dielectric layer **64** is formed of a nitride such as silicon nitride, an oxide such as silicon oxide, PhosphoSilicate Glass (PSG), BoroSilicate Glass (BSG), Boron-doped PhosphoSilicate Glass (BPSG), or the like. As shown in FIG. 2B, the redistribution wirings **66** are formed over the dielectric layer **64**. The formation of the redistribution wirings **66** may include forming a seed layer (not shown) over the dielectric layer **64**, forming a patterned mask (not shown) such as a photoresist layer over the seed layer, and then performing a plating process on the exposed seed layer. The patterned mask and the portions of the seed layer covered by the patterned mask are then removed, leaving the redistribution wirings **66** as shown in FIG. 2B. In accordance with some embodiments, the seed layer includes a titanium layer and a copper layer over the titanium layer. The seed layer may be formed using, for example, Physical Vapor Deposition (PVD). The plating may be performed using, for example, electroless plating. As shown in FIG. 2C, the dielectric layer **68** is formed over the dielectric layer **64** to cover the redistribution wirings **66**. The bottom surface of the dielectric layer **68** is in contact with the top surfaces of the redistribution wirings **66** and the dielectric layer **64**. In accordance with some embodiments of the present disclosure, the dielectric layer **68** is formed of a polymer, which may be a photo-sensitive material such as PBO, polyimide, BCB, or the like. In some embodiments, the dielectric layer **68** is formed of a nitride such as silicon nitride, an oxide such as silicon oxide, PSG, BSG, BPSG, or the like. The dielectric layer **68** is then patterned to form openings **70** therein. Hence, portions of the redistribution wirings **66** are exposed through the openings **70** in the dielectric layer **68**. FIG. 2C and the subsequent figures illustrate a single redistribution circuit structure **61** having single-layer redistribution wirings **66** for illustrative purposes and some embodiments may have a plurality of layers of redistribution wirings **66** by repeating the process discussed above.

(24) Referring to FIG. 2D, after forming the redistribution circuit structure **61** over the de-bonding layer **62** carried by the carrier **60**, metal posts **72** are formed on the redistribution circuit structure **61** and electrically connected to the redistribution wirings **66** of the redistribution circuit structure

61. Throughout the description, the metal posts **72** are also referred to as conductive through vias **72** since the metal posts **72** penetrate through the subsequently formed molding material (shown in FIG. **2G**). In some embodiments, the conductive through vias **72** are formed by plating. The plating of the conductive through vias **72** may include forming a blanket seed layer (not shown) over the dielectric layer **68** and extending into the openings **70** shown in FIG. **2C**, forming and patterning a photoresist (not shown), and plating the conductive through vias **72** on the portions of the seed layer that are exposed through the openings in the photoresist. The photoresist and the portions of the seed layer that were covered by the photoresist are then removed. The material of the conductive through vias **72** may include copper, aluminum, or the like. The conductive through vias **72** may have the shape of rods. The top-view shapes of the conductive through vias **72** may be circles, rectangles, squares, hexagons, or the like.

(25) Referring FIG. **2E**, after forming the conductive through vias **72**, at least one singulated SoIC die, e.g., such as that the singulated SoIC die **22** shown in FIG. **1D**, is picked-up and placed over the dielectric layer **68** of the redistribution circuit structure **61**. Only a single singulated SoIC die **22** and its surrounding conductive through vias **72** are illustrated in FIG. **2E** for illustrative purposes. It is noted, however, that the process steps shown in FIGS. **2A** through **2N** may be performed at wafer level, and are performed on all of the singulated SoIC dies **22** and the conductive through vias **72** disposed over the carrier **60** in some embodiments. As illustrated in FIG. **2E**, the top tier semiconductor dies **20** are stacked over the bottom tier semiconductor die **21**, and the back surface of the bottom tier semiconductor die **21** in the singulated SoIC die **22** is adhered to the dielectric layer **68** through the die-attachment film **19**. In some embodiments, the die-attachment film **19** is an adhesive film (e.g., epoxy film, silicone film, and so on).

(26) Referring to FIG. **2F**, an insulating encapsulation material **76** is formed over the redistribution circuit structure **61** to cover the SoIC die **22** and the conductive through vias **72**. The insulating encapsulation material **76** may be a molding compound (e.g., epoxy or other suitable resin) formed through an over-molding process. The insulating encapsulation material **76** fills the gaps between neighboring conductive through vias **72**, the gaps between the top tier semiconductor dies **20**, and the gaps between the conductive through vias **72** and the SoIC die **22**. The top surface of the insulating encapsulation material **76** is higher than the back surface of the top tier semiconductor dies **20** and the conductive through vias **72**.

(27) Next, as shown in FIG. **2G**, a planarization such as a Chemical Mechanical Polish (CMP) process and/or a mechanical grinding process is performed to partially remove the insulating encapsulation material **76** until the conductive through vias **72**, the substrates **12** and the through substrate vias **14** in the top tier semiconductor dies **20** are exposed. After the insulating encapsulation material **76** is thinned down, an insulating encapsulant **76'** is formed to laterally encapsulate the SoIC die **22** and the conductive through vias **72**. Due to the planarization, the top ends of conductive through vias **72** are substantially level or coplanar with the back surface of the top tier semiconductor dies **20**, and are substantially level or coplanar with the top surface of the insulating encapsulant **76'**, within process variations. In the illustrated exemplary embodiments, the planarization is performed until the conductive through vias **72** and the through substrate vias **14** in the top tier semiconductor dies **20** are exposed. The substrates **12** of the top tier semiconductor dies **20** are partially removed until the through substrate vias **14** are exposed.

(28) As shown in FIG. **2G**, the insulating encapsulant **76'** may fill the gaps between the top tier semiconductor dies **20**. Furthermore, the insulating encapsulant **76'** is in contact with the portions of the bonding dielectric layer **17a** of the bottom tier semiconductor die **21** which are not covered by the top tier semiconductor dies **20**. In some embodiments, the insulating encapsulant **76'** includes a first encapsulation portion **76a** and a second encapsulation portion **76b**. The first encapsulation portion **76a** covers the portions of the bonding dielectric layer **17a** of the bottom tier semiconductor die **21** which are not covered by the top tier semiconductor dies **20**. The first encapsulation portion **76a** fills the gaps between the top tier semiconductor dies **20** and is in

contact with sidewalls of the top tier semiconductor dies **20**. A thickness of the first encapsulation portion **76a** is substantially equal to that of the top tier semiconductor dies **20**. The second encapsulation portion **76b** laterally encapsulates the SoIC die **22** and the first encapsulation portion **76a**. Furthermore, the second encapsulation portion **76b** is continuous with the first encapsulation portion **76a** and in contact with sidewalls of the bottom tier semiconductor die **21**. The second encapsulation portion **76b** and the first encapsulation portion **76a** may be integrally formed as one-piece encapsulant, and have the same material. A thickness of the second encapsulation portion **76b** is substantially equal to an overall thickness of the SoIC die **22** and the die-attachment film **19**.

(29) FIG. 2H through 2M illustrate formation of a redistribution circuit structure **77** and solder regions. As shown in FIGS. 2H through 2L, a redistribution circuit structure **77** including a dielectric layer **78**, redistribution wirings **80**, a dielectric layer **82**, redistribution wirings **86**, and a dielectric layer **88** is formed on the substrates **12** and the insulating encapsulant **76'**. As shown in FIG. 2M, solder regions including Under-Bump Metallurgies (UBMs) **92** and electrical connectors **94** disposed on the UBMs **92** are formed on the redistribution circuit structure **77**.

(30) Referring to FIG. 2H, a dielectric layer **78** is formed on the top tier semiconductor dies **20** of the SoIC die **22** and the insulating encapsulant **76'**. In some embodiments, the dielectric layer **78** is formed of a polymer such as PBO, polyimide, or the like. In some embodiments, dielectric layer **78** is formed of silicon nitride, silicon oxide, or the like. The openings **79** are formed in the dielectric layer **78** to expose conductive through vias **72** and the through substrate vias **14**. The formation of the openings **79** may be performed through a photolithography process.

(31) Next, referring to FIG. 2I, redistribution wirings **80** are formed to connect to the through substrate vias **14** and the conductive through vias **72**. The redistribution wirings **80** may also interconnect the through substrate vias **14** and the conductive through vias **72**. The redistribution wirings **80** may include metal traces (metal lines) over the dielectric layer **78** as well as metal vias extending into the openings **79** (shown in FIG. 2H) to electrically connect to the conductive through vias **72** and the through substrate vias **14**. In some embodiments, the redistribution wirings **80** are formed in a plating process, wherein each of the redistribution wirings **80** includes a seed layer (not shown) and a plated metallic material over the seed layer. The seed layer and the plated material may be formed of the same material or different materials. The redistribution wirings **80** may comprise a metal or a metal alloy including aluminum, copper, tungsten, and alloys thereof. The redistribution wirings **80** are formed of non-solder materials. The via portions of the redistribution wirings **80** may be in physical contact with the top surfaces of the through substrate vias **14**.

(32) Referring to FIG. 2J, a dielectric layer **82** is formed over the redistribution wirings **80** and the dielectric layer **78**. The dielectric layer **82** may be formed using a polymer, which may be selected from the same candidate materials as those of the dielectric layer **78**. For example, the dielectric layer **82** may include PBO, polyimide, BCB, or the like. In some embodiments, the dielectric layer **82** may include non-organic dielectric materials such as silicon oxide, silicon nitride, silicon carbide, silicon oxynitride, or the like. The openings **84** are also formed in the dielectric layer **82** to expose the redistribution wirings **80**. The formation of the openings **84** may be performed through a photolithography process.

(33) Referring to FIG. 2K, FIG. 2K illustrates the formation of redistribution wirings **86**, which are electrically connected to the redistribution wirings **80**. The formation of the redistribution wirings **86** may adopt similar methods and materials to those for forming the redistribution wirings **80**.

(34) Referring to FIG. 2L, an additional dielectric layer **88**, which may be a polymer layer, is formed to cover the redistribution wirings **86** and the dielectric layer **82**. The dielectric layer **88** may be selected from the same candidate polymers used for forming the dielectric layers **78** and **82**. Opening(s) **90** are then formed in the dielectric layer **88** to expose the metal pad portions of redistribution wirings **86**. The formation of the openings **90** may be performed through a photolithography process.

(35) FIG. 2M illustrates the formation of the UBMs **92** and the electrical connectors **94** in accordance with some exemplary embodiments. Referring to FIG. 2M, the formation of the UBMs **92** may include deposition and patterning. The formation of the electrical connectors **94** may include placing solder on the exposed portions of the UBMs **92** and then reflowing the solder to form solder balls. In some embodiments, the formation of the electrical connectors **94** includes performing a plating step to form solder regions over redistribution wirings **86** and then reflowing the solder regions. The electrical connectors **94** may also include metal pillars or metal posts and solder caps, which may also be formed through plating. Throughout the description, the combined structure including the SoIC die **22**, the conductive through vias **72**, the insulating encapsulant **76'**, the redistribution circuit structures **61** and the redistribution circuit structures **77** will be referred to as a package **100**, which may be a composite wafer with a round top-view shape.

(36) Next, the package **100** is de-bonded from carrier **60**. The de-bonding layer **62** is also cleaned from the package **100**. The de-bonding may be performed by irradiating a light such as UV light or laser on the de-bonding layer **62** to decompose the de-bonding layer **62**. In the de-bonding process, a tape (not shown) may be adhered onto the dielectric layer **88** and the electrical connectors **94**. In subsequent steps, the carrier **60** and the de-bonding layer **62** are removed from the package **100**. A die saw process is performed to saw the package **100** into multiple Integrated Fan-out (InFO) packages, each including at least one SoIC die **22**, conductive through vias **72**, an insulating encapsulant **76'**, a redistribution circuit structures **61**, and a redistribution circuit structures **77**. One of the resulting packages is shown as a package **100** illustrated in FIG. 2N.

(37) FIG. 2N illustrates a package on package (PoP) structure in accordance with some embodiments of the present disclosure. Referring to FIG. 2N, another package **200** is provided and bonded with the package **102** such that a PoP structure is formed. In some embodiments of the present disclosure, the bonding between the package **200** and the package **102** is performed through solder regions **98**, which joins the metal pad portions of the redistribution wirings **66** to the metal pads in the package **200**. In some embodiments, the package **200** includes device dies **202**, which may be memory dies such as Static Random Access Memory (SRAM) dies, Dynamic Random Access Memory (DRAM) dies, or the like. The memory dies may also be bonded to package substrate **204** in some exemplary embodiments.

(38) FIGS. 3A through 3N are cross-sectional views schematically illustrating a process flow for fabricating integrated fan-out package structures of SoIC dies in accordance with some embodiments of the present disclosure.

(39) Referring to FIGS. 3A through 3D, since the processes illustrated in FIGS. 3A through 3D are the same as those illustrated in FIGS. 2A through 2D, detailed descriptions regarding to FIGS. 3A through 3D are thus omitted.

(40) Referring FIG. 3E, after forming the conductive through vias **72**, at least one singulated SoIC die **22** shown in FIG. 1D is picked-up and placed over the dielectric layer **68** of the redistribution circuit structure **61**. Only a single singulated SoIC die **22** and its surrounding conductive through vias **72** are illustrated in FIG. 3E for illustrative purposes. It is noted, however, that the process steps shown in FIGS. 3A through 3N may be performed on a plurality regions at a wafer level, and may be performed on all of the singulated SoIC dies **22** and the conductive through vias **72** disposed over the carrier **60** in some embodiments. As illustrated in FIG. 3E, the top tier semiconductor dies **20** are stacked over the bottom tier semiconductor die **21**, and the back surface of the bottom tier semiconductor die **21** in the singulated SoIC die **22** is adhered to the dielectric layer **68** through the die-attachment film **19**. In some embodiments, the die-attachment film **19** is an adhesive film (e.g., epoxy film, silicone film, and so on).

(41) After the singulated SoIC die **22** is mounted over the dielectric layer **68**, a removal process is performed to partially remove the substrates **12** of the top tier semiconductor dies **20** until the through substrate vias **14** protrude from the back surfaces of the substrates **12**. In some embodiments, the substrates **12** are silicon substrates, a silicon recessing process is performed to

partially remove (e.g., thin down) the substrates **12**, wherein an isotropic etch process is utilized to partially remove the substrates **12** such that the through substrate vias **14** protrude from the back surfaces of the substrates **12**, and an etchant used to etch the substrates **12** includes sulfur hexafluoride (SF₆) or other suitable etchant. Level height difference between the top ends of the through substrate vias **14** and the back surfaces of the substrates **12** may be in a range from about 1 micrometer to about 2 micrometers.

(42) Referring to FIG. 3F, an insulating encapsulation material **76** is formed over the redistribution circuit structure **61** to cover the SoIC die **22** and the conductive through vias **72**. The insulating encapsulation material **76** may be a molding compound (e.g., epoxy or other suitable resin) formed through an over-molding process. The insulating encapsulation material **76** fills the gaps between neighboring conductive through vias **72**, the gaps between the top tier semiconductor dies **20**, and the gaps between the conductive through vias **72** and the SoIC die **22**. The top surface of the insulating encapsulation material **76** is higher than the top ends of the through substrate vias **14**, the back surface of the top tier semiconductor dies **20** and the conductive through vias **72**.

(43) Next, as shown in FIG. 3G, a planarization such as a Chemical Mechanical Polish (CMP) process and/or a mechanical grinding process is performed to partially remove the insulating encapsulation material **76** until the conductive through vias **72** and the through substrate vias **14** protruding from the back surface of the top tier semiconductor dies **20** are exposed. After the insulating encapsulation material **76** is thinned down, an insulating encapsulant **76''** is formed to laterally encapsulate the SoIC die **22** and the conductive through vias **72**. Due to the planarization, the top ends of conductive through vias **72** and the top ends of the through substrate vias **14** are substantially level or coplanar with the top surface of the insulating encapsulant **76''**, within process variations. In the illustrated exemplary embodiments, the planarization is performed until the conductive through vias **72** and the through substrate vias **14** protruding from the top tier semiconductor dies **20** are exposed.

(44) As shown in FIG. 3G, the insulating encapsulant **76''** may fill the gaps between the top tier semiconductor dies **20**. The insulating encapsulant **76''** covers the back surface of the top tier semiconductor dies **20**. Furthermore, the insulating encapsulant **76''** is in contact with the portions of the bonding dielectric layer **17a** of the bottom tier semiconductor die **21** which are not covered by the top tier semiconductor dies **20**. In some embodiments, the insulating encapsulant **76''** includes a first encapsulation portion **76a**, a second encapsulation portion **76b**, and a third encapsulation portion **76c**. The first encapsulation portion **76a** covers the portions of the bonding dielectric layer **17a** of the bottom tier semiconductor die **21** which are not covered by the top tier semiconductor dies **20**. The first encapsulation portion **76a** fills the gaps between the top tier semiconductor dies **20** and is in contact with sidewalls of the top tier semiconductor dies **20**. The thickness **T1** of the first encapsulation portion **76a** is substantially equal to that of the top tier semiconductor dies **20**. The second encapsulation portion **76b** laterally encapsulates the SoIC die **22** and the first encapsulation portion **76a**. The second encapsulation portion **76b** is continuous with the first encapsulation portion **76a** and in contact with sidewalls of the bottom tier semiconductor die **21**. The thickness **T2** of the second encapsulation portion **76b** is substantially equal to an overall thickness of the SoIC die **22** and the die-attachment film **19**. Furthermore, the third encapsulation portion **76c** covers the back surfaces of the top tier semiconductor dies **20** and laterally encapsulates the through substrate vias **14** protruding from the back surfaces of the top tier semiconductor dies **20**. In other words, the through substrate vias **14** protruding from the back surfaces of the top tier semiconductor dies **20** penetrate through the third encapsulation portion **76c**. The third encapsulation portion **76c** is laterally surrounded by and continuous with the first encapsulation portion **76a**. The thickness **T3** of the third encapsulation portion **76c** may range from about 1 micrometer to about 2 micrometers. It is noted that, the substrates **12** of the top tier semiconductor dies **20** are still covered by the third encapsulation portion **76c** and not revealed at this stage.

(45) FIGS. 3H through 3M illustrate formation of a redistribution circuit structure 77 and solder regions. As shown in FIGS. 3H through 3L, a redistribution circuit structure 77 including a dielectric layer 78, redistribution wirings 80, a dielectric layer 82, redistribution wirings 86, and a dielectric layer 88 is formed on the top ends of conductive through vias 72, the top ends of the through substrate vias 14, and the insulating encapsulant 76". The redistribution circuit structure 77 is spaced apart from the substrates 12 by the insulating encapsulant 76". As shown in FIG. 3M, solder regions including Under-Bump Metallurgies (UBMs) 92 and electrical connectors 94 disposed on the UBMs 92 are formed on the redistribution circuit structure 77.

(46) Referring to FIGS. 3H through 3N, similar processes and materials may be used as those discussed above with reference to FIGS. 2H through 2N.

(47) FIGS. 4A through 4N are cross-sectional views schematically illustrating a process flow for fabricating integrated fan-out package structures of SoIC dies in accordance with some alternative embodiments of the present disclosure.

(48) Referring to FIGS. 4A through 4D, similar processes and/or materials may be used as those discussed above with reference to FIGS. 2A through 2D.

(49) Referring FIG. 4E, after forming the conductive through vias 72, at least one singulated SoIC die, such as the singulated SoIC die 22 shown in FIG. 1D, is picked-up and placed over the dielectric layer 68 of the redistribution circuit structure 61. Only a single singulated SoIC die 22 and its surrounding conductive through vias 72 are illustrated in FIG. 4E for illustrative purposes. It is noted, however, that the process steps shown in FIGS. 4A through 4N may be performed on a plurality of regions at a wafer level, and may be performed on all of the singulated SoIC dies 22 and the conductive through vias 72 disposed over the carrier 60 in some embodiments. As illustrated in FIG. 4E, the top tier semiconductor dies 20 are stacked over the bottom tier semiconductor die 21, and the back surface of the bottom tier semiconductor die 21 in the singulated SoIC die 22 is adhered to the dielectric layer 68 through the die-attachment film 19. In some embodiments, the die-attachment film 19 is an adhesive film (e.g., epoxy film, silicone film, and so on).

(50) After the singulated SoIC die 22 is mounted over the dielectric layer 68, a removal process is performed to partially remove the substrates 12 of the top tier semiconductor dies 20 until the through substrate vias 14 protrude from the back surfaces of the substrates 12. In some embodiments, the substrates 12 are silicon substrates, a silicon recessing process is performed to partially remove (e.g., thin down) the substrates 12, wherein an isotropic etch process is utilized to partially remove the substrates 12 such that the through substrate vias 14 protrude from the back surfaces of the substrates 12, and an etchant used to etch the substrates 12 includes sulfur hexafluoride (SF₆) or other suitable etchant. Level height difference between the top ends of the through substrate vias 14 and the back surfaces of the substrates 12 may be in a range from about 1 micrometer to about 2 micrometers.

(51) After the partial removal process of the substrates 12 is performed, a dielectric layer 74 is conformally formed over the redistribution circuit structure 61 to cover the SoIC die 22 and the conductive through vias 72. In some embodiments, the material of the dielectric layer 74 may be silicon oxide (SiO_x, where x>0), silicon nitride (SiN_x, where x>0), silicon oxynitride (SiO_xN_y, where x>0 and y>0) or other suitable dielectric material. The thickness of the dielectric layer 74 may range from about 4 micrometers to about 6 micrometers.

(52) Referring to FIG. 4F, an insulating encapsulation material 76 is formed on the dielectric layer 74 which covers the redistribution circuit structure 61, the SoIC die 22 and the conductive through vias 72. The insulating encapsulation material 76 may be a molding compound (e.g., epoxy or other suitable resin) formed through an over-molding process. The insulating encapsulation material 76 fills the gaps between neighboring conductive through vias 72, the gaps between the top tier semiconductor dies 20, and the gaps between the conductive through vias 72 and the SoIC die 22. The top surface of the insulating encapsulation material 76 is higher than the top ends of the

through substrate vias **14**, the back surface of the top tier semiconductor dies **20** and the conductive through vias **72**.

(53) Next, as shown in FIG. **4G**, a planarization such as a Chemical Mechanical Polish (CMP) process and/or a mechanical grinding process is performed to partially remove the insulating encapsulation material **76** and the dielectric layer **74** until the through substrate vias **14** protruding from the top tier semiconductor dies **20** are exposed. After the insulating encapsulation material **76** and the dielectric layer **74** are partially removed, an insulating encapsulant **76'''** is formed to laterally encapsulate the SoIC die **22** and the conductive through vias **72**. Due to the planarization, the top ends of conductive through vias **72** and the top ends of the through substrate vias **14** are substantially level or coplanar with the top surface of the insulating encapsulant **76'''**, within process variations. In the illustrated exemplary embodiments, the planarization is performed until the through substrate vias **14** protruding from the top tier semiconductor dies **20** are exposed. Furthermore, after forming the insulating encapsulant **76'''**, a portion of the dielectric layer **74** which covers the back surfaces of the top tier semiconductor dies **20** are exposed, and the top surface of the exposed portion of the dielectric layer **74** is substantially level or coplanar with the top surface of the insulating encapsulant **76'''**, within process variations.

(54) As shown in FIG. **4G**, the insulating encapsulant **76'''** may fill the gaps between the top tier semiconductor dies **20**. The insulating encapsulant **76'''** is spaced apart from the SoIC die **22** and the conductive through vias **72** by the dielectric layer **74**. In some embodiments, the insulating encapsulant **76'''** includes a first encapsulation portion **76a** and a second encapsulation portion **76b**. The first encapsulation portion **76a** is disposed on the dielectric layer **74** and is located above portions of the bonding dielectric layer **17a** of the bottom tier semiconductor die **21** which are not covered by the top tier semiconductor dies **20**. The first encapsulation portion **76a** fills the gaps between the top tier semiconductor dies **20** and is spaced apart from sidewalls of the top tier semiconductor dies **20** by the dielectric layer **74**. By depositing the dielectric layer **74**, the first encapsulation portion **76a** is spaced apart from the portions of the bonding dielectric layer **17a** of the bottom tier semiconductor die **21** which are not covered by the top tier semiconductor dies **20**. The through substrate vias **14** protruding from the back surfaces of the top tier semiconductor dies **20** penetrate through the dielectric layer **74**. The thickness **T1** of the first encapsulation portion **76a** is less than that of the top tier semiconductor dies **20** due to the dielectric layer **74**. The second encapsulation portion **76b** laterally encapsulates the SoIC die **22** and the first encapsulation portion **76a**. The second encapsulation portion **76b** is continuous with the first encapsulation portion **76a** and spaced apart from sidewalls of the top tier semiconductor die **20** and the bottom tier semiconductor die **21** by the dielectric layer **74**. Furthermore, the second encapsulation portion **76b** is spaced apart from the conductive through vias **72** and the redistribution circuit structure **61** by the dielectric layer **74**. The thickness **T2** of the second encapsulation portion **76b** is less than an overall thickness of the SoIC die **22** and the die-attachment film **19** due to the dielectric layer **74**. It is noted that, the substrates **12** of the top tier semiconductor dies **20** are still covered by the dielectric layer **74** and not revealed at this stage.

(55) FIG. **4H** through **4M** illustrate formation of a redistribution circuit structure **77** and solder regions. As shown in FIGS. **4H** through **4L**, a redistribution circuit structure **77** including a dielectric layer **78**, redistribution wirings **80**, a dielectric layer **82**, redistribution wirings **86**, and a dielectric layer **88** is formed on the top ends of conductive through vias **72**, the top ends of the through substrate vias **14**, and the insulating encapsulant **76'''**, wherein the dielectric layer **78** covers the dielectric layer **74**, the insulating encapsulant **76'''** and the conductive through vias **72**. The redistribution circuit structure **77** is spaced apart from the SoIC die **22** by the dielectric layer **74**. As shown in FIG. **4M**, solder regions including Under-Bump Metallurgies (UBMs) **92** and electrical connectors **94** disposed on the UBMs **92** are formed on the redistribution circuit structure **77**.

(56) Referring to FIGS. **4H** through **4M**, similar processes and materials may be used as discussed

above with reference to FIGS. 2H through 2M.

(57) In the above-mentioned embodiments, since the insulating encapsulant **76'**, **76''** and **76'''** are formed through a single molding process followed by a CMP process and/or a mechanical grinding process, process time and manufacturing cost may be reduced. Furthermore, reliability and process yield may be enhanced.

(58) In accordance with some embodiments of the disclosure, a package structure including a device die, an insulating encapsulant, and a first redistribution circuit is provided. The device die includes a first semiconductor die and a second semiconductor die. The first semiconductor die is stacked over and electrically connected to the second semiconductor die. The insulating encapsulant laterally encapsulates the device die. The insulating encapsulant includes a first encapsulation portion and a second encapsulation portion connected to the first encapsulation portion. The first encapsulation portion is disposed on the second semiconductor die and laterally encapsulates the first semiconductor die. The second encapsulation portion laterally encapsulates the first insulating encapsulation and the second semiconductor die. The first redistribution circuit structure is disposed on the device die and a first surface of the insulating encapsulant, and the first redistribution circuit structure is electrically connected to the device die. In some embodiments, the first semiconductor die comprising a first bonding structure, the second semiconductor die comprising a second bonding structure, and the first bonding structure is bonded to the second bonding structure. In some embodiments, the first bonding structure comprises a first bonding dielectric layer and first bonding conductors embedded in the first bonding dielectric layer, the second bonding structure comprises a second bonding dielectric layer and first bonding conductors embedded in the second bonding dielectric layer, the first bonding conductors are bonded with the second bonding conductors, and the first bonding dielectric layer is bonded with a first portion of the second bonding dielectric layer. In some embodiments, the first encapsulation portion of the insulating encapsulant is in contact with a second portion of the second bonding dielectric layer, and the second portion of the second bonding dielectric layer is not covered by the first bonding dielectric layer. In some embodiments, the first encapsulation portion of the insulating encapsulant is in contact with sidewalls of the first semiconductor die, and the second encapsulation portion of the insulating encapsulant is in contact with sidewalls of the second semiconductor die. In some embodiments, the insulating encapsulant further comprises a third encapsulation portion disposed on the first semiconductor die, the third encapsulation portion is connected to and laterally encapsulated by the first encapsulation portion. In some embodiments, the first semiconductor die comprises through semiconductor vias penetrating through the third encapsulation portion and electrically connected to the first redistribution circuit structure. In some embodiments, the package structure further includes a dielectric layer covering the device die, wherein the device die is spaced apart from the insulating encapsulant by the dielectric layer. In some embodiments, the package structure further includes: a conductive through vias disposed aside the device die, wherein the conductive through vias penetrate through the second encapsulation portion of the insulating encapsulant; and a second redistribution circuit structure disposed on the device die and a second surface of the insulating encapsulant, wherein the second redistribution circuit structure is electrically connected to the first redistribution circuit structure through the conductive through vias. In some embodiments, the package structure further includes a dielectric layer covering the device die and sidewalls of the conductive through vias, wherein the device die and the conductive through vias are spaced apart from the insulating encapsulant by the dielectric layer.

(59) In accordance with some other embodiments of the disclosure, a package structure including a bottom tier semiconductor die, at least one top tier semiconductor die, an insulating encapsulant, and a first redistribution circuit structure is provided. The bottom tier semiconductor die includes a first semiconductor substrate, a first interconnect structure disposed on the first semiconductor die, and a first bonding structure disposed on and electrically connected to the first interconnect structure. The at least one top tier semiconductor die includes a second semiconductor substrate,

through semiconductor vias protruding from a back surface of the second semiconductor substrate, a second interconnect structure disposed on the second semiconductor die, and a second bonding structure disposed on and electrically connected to the second interconnect structure. The second bonding structure is bonded with a portion of the first bonding structure, and a lateral dimension of the bottom tier semiconductor die is greater than that of the top tier semiconductor die. The insulating encapsulant covers the first semiconductor die and the second semiconductor die. The first redistribution circuit structure is disposed on the top tier semiconductor and a top surface of the insulating encapsulant, wherein the through semiconductor vias penetrate through the insulating encapsulant and electrically connected to the first redistribution circuit structure. In some embodiment, a portion of the insulating encapsulant covers the back surface of the second semiconductor substrate, and the through semiconductor vias penetrate through the portion of the insulating encapsulant. In some embodiment, the insulating encapsulant includes a first encapsulation portion disposed on and in contact with the first bonding structure of the bottom tier semiconductor die; a second encapsulation portion laterally encapsulating the first encapsulation portion and the bottom tier semiconductor die; and a third encapsulation portion covering the back surface of the second semiconductor substrate of the top tier semiconductor die, wherein the first encapsulation portion laterally encapsulates the third encapsulation portion and the top tier semiconductor die. In some embodiment, the top tier semiconductor die is spaced apart from the first redistribution circuit structure by the insulating encapsulant. In some embodiment, the package structure further includes a conductive through vias penetrating through the insulating encapsulant; and a second redistribution circuit structure disposed on a bottom surface of the insulating encapsulant, wherein the second redistribution circuit structure is electrically connected to the first redistribution circuit structure through the conductive through vias.

(60) In accordance with some other embodiments of the disclosure, a package structure including a bottom tier semiconductor die, at least one top tier semiconductor die, a dielectric layer, and an insulating encapsulant is provided. The at least one top tier semiconductor die is bonded with the bottom tier semiconductor die, a lateral dimension of the bottom tier semiconductor die is greater than that of the top tier semiconductor die, and the top tier semiconductor die includes through semiconductor vias protruding from a back surface thereof. The dielectric layer covering the bottom tier semiconductor die and the top tier semiconductor die, and the through semiconductor vias penetrate through a portion of the dielectric layer which covers the back surface of the top tier semiconductor die. The insulating encapsulant laterally encapsulates the first semiconductor die and the second semiconductor die such that the bottom tier semiconductor die and the top tier semiconductor die are spaced apart from the insulating encapsulant by the dielectric layer. In some embodiments, the package structure further includes a first redistribution circuit structure disposed on the top tier semiconductor and a top surface of the insulating encapsulant, wherein the through semiconductor vias penetrate through the portion of the dielectric layer and electrically connected to the first redistribution circuit structure. In some embodiments, the first redistribution circuit structure is spaced apart from the insulating encapsulant by the dielectric layer. In some embodiments, the package structure further includes: a conductive through vias penetrating through the insulating encapsulant; and a second redistribution circuit structure disposed on a bottom surface of the insulating encapsulant, wherein the second redistribution circuit structure is electrically connected to the first redistribution circuit structure through the conductive through vias. In some embodiments, the conductive through vias and the second redistribution circuit structure are spaced apart from the insulating encapsulant by the dielectric layer.

(61) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such

equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A method of forming a semiconductor structure, the method comprising: bonding a first semiconductor die to a first surface of a second semiconductor die, wherein the first semiconductor die is electrically connected to the second semiconductor die; laterally encapsulating the first semiconductor die and the second semiconductor die with an encapsulant, the encapsulant comprising a first encapsulation portion and a second encapsulation portion continuous with the first encapsulation portion, the first encapsulation portion being disposed on the second semiconductor die and laterally encapsulating the first semiconductor die, and the second encapsulation portion laterally encapsulating the first encapsulation portion and the second semiconductor die; and forming a first redistribution circuit structure on the first semiconductor die and a first surface of the encapsulant, wherein the first redistribution circuit structure is electrically connected to the first semiconductor die.
2. The method of claim 1, further comprising: after bonding the first semiconductor die to the second semiconductor die, attaching the second semiconductor die to a first substrate.
3. The method of claim 2, further comprising: prior to attaching the second semiconductor die to the first substrate, forming the first substrate by forming a second redistribution structure on a carrier substrate.
4. The method of claim 2, further comprising: forming through vias on the first substrate, wherein laterally encapsulating comprises laterally encapsulating the through vias.
5. The method of claim 1, wherein the first semiconductor die comprises a first bonding structure, wherein the first bonding structure comprises a first bonding dielectric layer and first bonding conductors embedded in the first bonding dielectric layer, wherein the second semiconductor die comprises a second bonding structure, wherein the second bonding structure comprises a second bonding dielectric layer and second bonding conductors embedded in the second bonding dielectric layer, the first bonding conductors are bonded to the second bonding conductors using direct metal-to-metal bonds, and the first bonding dielectric layer is bonded to a first portion of the second bonding dielectric layer by direct dielectric-to-dielectric bonds.
6. The method of claim 1, wherein the encapsulant contacts the first surface of the second semiconductor die.
7. The method of claim 1, wherein the encapsulant contacts sidewalls of the second semiconductor die.
8. A method of forming a semiconductor structure, the method comprising: bonding a top tier semiconductor die to a bottom tier semiconductor die, the top tier semiconductor die comprising a first semiconductor substrate, a first interconnect structure disposed on the first semiconductor substrate, and a first bonding structure disposed on and electrically connected to the first interconnect structure, the bottom tier semiconductor die comprising a second semiconductor substrate, a second interconnect structure disposed on the second semiconductor substrate, and a second bonding structure disposed on and electrically connected to the second interconnect structure, the first bonding structure being bonded with a portion of the second bonding structure, wherein a lateral dimension of the bottom tier semiconductor die is greater than a lateral dimension of the top tier semiconductor die; encapsulating the bottom tier semiconductor die and the top tier semiconductor die with an encapsulant, wherein the encapsulant extends over an upper surface of the bottom tier semiconductor die and along sidewalls of the top tier semiconductor die; and forming a first redistribution structure disposed on the top tier semiconductor die and a top surface of the encapsulant, wherein the first redistribution structure comprises a conductive element

electrically coupled to a through via protruding from a back surface of the first semiconductor substrate.

9. The method of claim 8, wherein the encapsulant extends over an upper surface of the top tier semiconductor die.

10. The method of claim 9, wherein the through via extends through the encapsulant.

11. The method of claim 9, wherein the encapsulant extends along sidewalls of the through via.

12. The method of claim 8, further comprising: forming a second redistribution structure on a carrier wafer; and after bonding the top tier semiconductor die to the bottom tier semiconductor die, attaching the bottom tier semiconductor die to the second redistribution structure.

13. The method of claim 12, wherein attaching the bottom tier semiconductor die to the second redistribution structure is performed using an adhesive layer.

14. The method of claim 12, further comprising: after attaching the bottom tier semiconductor die to the second redistribution structure, thinning the back surface of the first semiconductor substrate to cause the through via to protrude from the back surface of the first semiconductor substrate.

15. The method of claim 8, further comprising: forming a dielectric layer covering the bottom tier semiconductor die and the top tier semiconductor die, wherein the through via penetrates through a portion of the dielectric layer on a back surface of the top tier semiconductor die.

16. A method of forming a semiconductor structure, the method comprising: bonding a top tier semiconductor die to a bottom tier semiconductor die, a lateral dimension of the bottom tier semiconductor die being greater than a lateral dimension of the top tier semiconductor die, and the top tier semiconductor die comprising through vias exposed at a back surface of the top tier semiconductor die; forming a dielectric layer over the bottom tier semiconductor die and the top tier semiconductor die, wherein the through vias penetrate through a portion of the dielectric layer on the back surface of the top tier semiconductor die; and encapsulating the bottom tier semiconductor die and the top tier semiconductor die with an encapsulant such that the bottom tier semiconductor die and the top tier semiconductor die are spaced apart from the encapsulant by the dielectric layer.

17. The method of claim 16, further comprising: forming a first redistribution structure over a carrier substrate; and after bonding the top tier semiconductor die to the bottom tier semiconductor die, attaching the bottom tier semiconductor die to the first redistribution structure.

18. The method of claim 17, further comprising: forming a second redistribution structure over the encapsulant, the top tier semiconductor die, and the bottom tier semiconductor die.

19. The method of claim 17, further comprising: forming a conductive post over the first redistribution structure, wherein forming the dielectric layer comprises forming the dielectric layer along sidewalls of the conductive post, wherein encapsulating comprises encapsulating the conductive post.

20. The method of claim 16, wherein the top tier semiconductor die is direct bonded to the bottom tier semiconductor die.
