

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12412871
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Kim; Jihoon

Semiconductor package utilizing a hybrid bonding process and method of manufacturing the same

Abstract

A semiconductor package includes a first semiconductor chip and a second semiconductor chip. The first semiconductor chip includes a peripheral region having a groove and a bonding region that is disposed higher than the groove. The second semiconductor chip is disposed in the bonding region of the first semiconductor chip. The second semiconductor chip is directly electrically connected to the first semiconductor chip. The second semiconductor chip includes an overhang protruded from the bonding region. The overhang is spaced apart from a bottom surface of the groove. Thus, a bonding failure, which may be caused by particles generated during a cutting the wafer and adhered to the edge portion of the second semiconductor chip, between the first semiconductor chip and the second semiconductor chip might be avoided.

Inventors:	Kim; Jihoon (Cheonan-si, KR)
Applicant:	SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR)
Family ID:	81586867
Assignee:	SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR)
Appl. No.:	18/518591
Filed:	November 23, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20240088105 A1	Mar. 14, 2024

Foreign Application Priority Data

KR	10-2020-0151642	Nov. 13, 2020
----	-----------------	---------------

Related U.S. Application Data

continuation parent-doc US 17367005 20210702 US 11855044 child-doc US 18518591

Publication Classification

Int. Cl.: **H01L25/065** (20230101); **H01L23/31** (20060101); **H01L23/48** (20060101)

U.S. Cl.:

CPC **H01L25/0657** (20130101); **H01L23/3107** (20130101); **H01L23/481** (20130101);
H01L2225/06517 (20130101)

Field of Classification Search

CPC: H01L (23/5386); H01L (23/13); H01L (25/0657)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8102060	12/2011	Plossl et al.	N/A	N/A
9142532	12/2014	Suga et al.	N/A	N/A
9502391	12/2015	Kwon	N/A	H01L 23/5389
10186500	12/2018	Ryu	N/A	H01L 24/19
10497675	12/2018	Kwak et al.	N/A	N/A
2005/0062166	12/2004	Kang	257/E29.022	H10D 62/117
2015/0155266	12/2014	Kim	257/737	H01L 24/06
2015/0235995	12/2014	Park	257/773	H01L 23/49822
2016/0005714	12/2015	Lee	257/777	H01L 23/367
2017/0186728	12/2016	Chainer	N/A	H01L 23/3738
2017/0358558	12/2016	Lee	N/A	H01L 25/0657
2018/0033779	12/2017	Park	N/A	H01L 23/5386
2018/0211937	12/2017	Lee	N/A	H01L 25/0657
2019/0139938	12/2018	Andry	N/A	H01L 25/0657
2019/0206844	12/2018	Lee	N/A	H01L 25/50
2019/0385995	12/2018	Metras	N/A	H01L 23/481
2020/0111763	12/2019	Hong	N/A	H01L 24/08
2020/0135698	12/2019	Hong et al.	N/A	N/A
2020/0178437	12/2019	Wimplinger	N/A	N/A

2020/0411472	12/2019	Chung	N/A	H01L 25/0657
2022/0157779	12/2021	Kim	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
6395600	12/2017	JP	N/A
20180170368	12/2017	JP	N/A
10-2020-0048771	12/2007	KR	N/A
10-2017-0065397	12/2016	KR	N/A

OTHER PUBLICATIONS

Office Action dated Apr. 16, 2025 issued in corresponding Korean Patent Application No. 10-2020-0151642. (Note: Kr 10-2017-0140985A previously cited.). cited by applicant

Primary Examiner: Diallo; Mamadou L

Attorney, Agent or Firm: MORGAN, LEWIS & BOCKIUS LLP

Background/Summary

CROSS-RELATED APPLICATIONS (1) This application is a Continuation of co-pending U.S. patent application Ser. No. 17/367,005, filed on Jul. 2, 2021, which claims priority under 35 USC § 119 to Korean Patent Application No. 10-2020-0151642, filed on Nov. 13, 2020 in the Korean Intellectual Property Office (KIPO), the contents of which are herein incorporated by reference in their entirety.

TECHNICAL FIELD

(1) The present disclosure relates to a semiconductor package and a method of manufacturing the same. More particularly, the present disclosure relates to a semiconductor package including a first semiconductor chip and a second semiconductor chip bonded to the first semiconductor chip by a hybrid bonding process, and a method of manufacturing the semiconductor package.

DISCUSSION OF THE RELATED ART

(2) Recently, a second semiconductor chip may be electrically connected, directly, to a first semiconductor chip by a hybrid bonding process. Thus, the generation of a joint gap between the first semiconductor chip and the second semiconductor chip can be avoided.

(3) According to related arts, during the cutting of a wafer including a plurality of the second semiconductor chips, a high concentration of particles may be generated at an edge portion of the second semiconductor chip.

(4) When the second semiconductor chip is be bonded to the first semiconductor chip by the hybrid bonding process, the edge portion of the second semiconductor chip might not make proper contact with the first semiconductor chip due to the presence of the particles. Thus, the second semiconductor chip might not be properly electrically connected to the first semiconductor chip and so a bonding failure may be generated.

SUMMARY

(5) A semiconductor package includes a first semiconductor chip, a second semiconductor chip and a molding member. The first semiconductor chip includes a plurality of connection vias and a wiring connected to lower ends of the connection vias. The second semiconductor chip is disposed on a central portion of an upper surface of the first semiconductor chip. The second semiconductor

chip includes bonding pads directly contacting upper ends of the connection vias. The molding member is formed on the upper surface of the first semiconductor chip and at least partially surrounds the second semiconductor chip. The connection vias are disposed on the central portion of the upper surface of the first semiconductor chip. The central portion of the upper surface of the first semiconductor chip is positioned on a plane that is higher than a plane on which an edge portion of the upper surface of the first semiconductor chip is positioned, relative to a package substrate. An edge portion of the second semiconductor chip includes an overhang horizontally protruded from the central portion of the upper surface of the first semiconductor chip. The overhang is spaced apart from the edge portion of the upper surface of the first semiconductor chip. The overhang has a horizontal length of about 3/20 times to about 9/20 times a width of the second semiconductor chip. A distance between a lower surface of the overhang and the edge portion of the upper surface of the first semiconductor chip is no less than about 8 μm .

(6) A semiconductor package includes a first semiconductor chip and a second semiconductor chip. The first semiconductor chip includes a peripheral region having a groove and a bonding region positioned higher than the groove, relative to a package substrate. The second semiconductor chip is disposed in the bonding region of the first semiconductor chip. The second semiconductor chip is directly electrically connected to the first semiconductor chip. The second semiconductor chip includes an overhang protruded from the bonding region. The overhang is spaced apart from a bottom surface of the groove.

(7) A method of manufacturing a semiconductor package utilizes a wafer that includes a plurality of first semiconductor chips. The wafer has a plurality of bonding regions and peripheral region surrounding each of the bonding regions. A groove is formed at an upper surface in the peripheral regions to upwardly protrude the bonding regions more than the peripheral regions. A plurality of second semiconductor chips, each of which has a size larger than a size of the bonding region, are hybrid-bonded to the bonding regions to form an overhang at an edge portion of each of the second semiconductor chip. The overhang is spaced apart from a bottom surface of the groove. The wafer is then cut along the peripheral regions.

(8) A semiconductor package includes a first semiconductor chip, a second semiconductor chip, a lower redistribution layer (RDL) structure, and a molding member. The first semiconductor chip includes a peripheral region having a groove and a bonding region positioned higher than the groove relative to a package substrate. The second semiconductor chip is disposed in the bonding region of the first semiconductor chip. The second semiconductor chip is directly electrically connected to the first semiconductor chip. The second semiconductor chip includes an overhang protruded from the bonding region. The overhang is spaced apart from a bottom surface of the groove. The lower RDL structure is disposed under the first semiconductor chip. The lower RDL structure is electrically connected to the first semiconductor chip. The molding member is formed on an upper surface of the lower RDL structure and at least partially surrounds the first semiconductor chip and the second semiconductor chip.

(9) A semiconductor package includes a package substrate, a logic chip, at least one first semiconductor chip and at least two stacked second semiconductor chips. The logic chip is disposed on an upper surface of the package substrate. The logic chip includes a first bonding region, a second bonding region, and a peripheral region at least partially surrounding each of the first and second bonding regions. The first semiconductor chip is disposed in the first bonding region of the logic chip. The first semiconductor chip is directly electrically connected to the logic chip. The second semiconductor chips are stacked in the second bonding region of the logic chip. The second semiconductor chips are directly electrically connected to the logic chip. The peripheral region of the logic chip has a groove. The peripheral region is positioned lower than the first and second bonding regions, relative to a package substrate. The first semiconductor chip includes a first overhang protruded from the first bonding region. The first overhang is spaced apart from a bottom surface of the groove. At least one of the second semiconductor chips includes a second

overhang protruded from the second bonding region. The second overhang is spaced apart from a bottom surface of the groove.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) A more complete appreciation of the present disclosure and many of the attendant aspects thereof will be readily obtained as the same becomes better understood by reference to the following detailed description when considered in connection with the accompanying drawings, wherein:
- (2) FIG. 1 is a cross-sectional view illustrating a semiconductor package in accordance with example embodiments of the present disclosure;
- (3) FIG. 2 is a cross-sectional view taken along a line A-A' in FIG. 1;
- (4) FIG. 3 is a plan view illustrating a method of manufacturing the semiconductor package in FIG. 1;
- (5) FIGS. 4 to 8 are cross-sectional views illustrating a method of manufacturing the semiconductor package in FIG. 1;
- (6) FIG. 9 is a cross-sectional view illustrating a semiconductor package in accordance with example embodiments of the present disclosure;
- (7) FIG. 10 is a cross-sectional view taken along a line B-B' in FIG. 9;
- (8) FIGS. 11 to 15 are cross-sectional views illustrating a method of manufacturing the semiconductor package in FIG. 9;
- (9) FIG. 16 is a cross-sectional view illustrating a semiconductor package in accordance with example embodiments of the present disclosure;
- (10) FIG. 17 is a cross-sectional view illustrating a semiconductor package in accordance with example embodiments of the present disclosure;
- (11) FIG. 18 is a cross-sectional view illustrating a semiconductor package in accordance with example embodiments of the present disclosure; and
- (12) FIG. 19 is a cross-sectional view illustrating a semiconductor package in accordance with example embodiments of the present disclosure.

DETAILED DESCRIPTION OF THE EMBODIMENTS

- (13) Hereinafter, example embodiments of the present disclosure will be explained in detail with reference to the accompanying drawings.
- (14) FIG. 1 is a cross-sectional view illustrating a semiconductor package in accordance with example embodiments of the present disclosure, and FIG. 2 is a cross-sectional view taken along a line A-A' in FIG. 1.
- (15) Referring to FIGS. 1 and 2, a semiconductor package 100 may include a first semiconductor chip 110, a second semiconductor chip 120, a molding member 150 and conductive bumps 160.
- (16) The first semiconductor chip 110 may include a plurality of connection vias 116. The connection vias 116 may be vertically disposed in the first semiconductor chip 110. Each of the connection vias 116 may include an upper end exposed through an upper surface of the first semiconductor chip 110, and a lower end exposed through a lower surface of the first semiconductor chip 110. The connection vias 116 may include through silicon vias (TSV).
- (17) An upper insulation layer 130 may be formed on the upper surface of the first semiconductor chip 110. The upper insulation layer 130 may have openings exposing the connection vias 116. Further, a lower insulation layer 132 may be formed on the lower surface of the first semiconductor chip 110. The upper insulation layer 130 and the lower insulation layer 132 may include an insulation material such as oxide, but the present disclosure is not necessarily limited to this arrangement. The lower insulation layer 132 may be considered a package substrate.

(18) A wiring **118** may be disposed in the lower insulation layer **132**. The wiring **118** may include an upper end exposed through an upper surface of the lower insulation layer **132**, and a lower end exposed through a lower surface of the lower insulation layer **132**. The upper end of the wiring **118** may be electrically connected to the lower end of the connection via **116**. The wiring **118** may have a steplike stack structure, but the present disclosure is not necessarily limited to this arrangement.

(19) The first semiconductor chip **110** may be divided into a bonding region B and a peripheral region P. The second semiconductor chip **120** may be disposed over the first semiconductor chip **110**. For example, the second semiconductor chip **120** may be disposed in the bonding region B to be electrically connected to the first semiconductor chip **120**. In contrast, the peripheral region P might not be electrically connected to the second semiconductor chip **120**. Thus, the upper ends of the connection vias **116** may be disposed on an upper surface of the bonding region B.

(20) In example embodiments of the present disclosure, the bonding region B may have a rectangular shape positioned at a central portion of the upper surface of the first semiconductor chip **110**. The peripheral region P may correspond to an edge portion of the upper surface of the first semiconductor chip **110** configured to surround the bonding region B. Thus, the peripheral region P may have a rectangular frame shape.

(21) The bonding region B may be upwardly protruded from the peripheral region P. For example, the upper surface of the bonding region B may be higher than an upper surface of the peripheral region P, with respect to a level of the package substrate, which may be considered to be the lower insulation layer **132**. The protruded structure of the bonding region B may be obtained by forming a groove **112** at the peripheral region P. For example, when the groove **112** may be formed along the peripheral region P, the upper surface of the peripheral region B may become lower than the upper surface of the bonding region B to provide the bonding region B with the upwardly protruded structure than the peripheral region P.

(22) In example embodiments of the present disclosure, the groove **112** may have a depth D of no less than about 8 μm , but the present disclosure is not necessarily limited to this arrangement. The depth D of the groove **112** is described in further detail below.

(23) In example embodiments of the present disclosure, the groove **112** may be wholly formed along the peripheral region P. Thus, the groove **112** may have a width that is substantially the same as a width of the peripheral region P. As a result, the whole upper surface of the peripheral region P may be positioned on a plane lower than a plane on which the upper surface of the bonding region B may be positioned. Further, the upper insulation layer **130** may be formed along the upper surfaces of the bonding region B and the peripheral region P. For example, the upper insulation layer **130** may be formed along an inner surface of the groove **112**.

(24) The second semiconductor chip **120** may include a plurality of bonding pads **122**. The bonding pads **122** may be disposed on a lower surface of the second semiconductor chip **120**. Thus, the lower surface of the second semiconductor chip **120** may correspond to an active face of the second semiconductor chip **120**. The second semiconductor chip **120** may have a rectangular shape corresponding to the rectangular bonding region B.

(25) The bonding pads **122** of the second semiconductor chip **120** may be directly connected to the connection vias **116** of the first semiconductor chip **110**. For example, the bonding pads **122** may directly contact the connection vias **116**. For example, the bonding pads **122** may be directly connected to the connection vias **116** by a hybrid bonding process. Thus, the lower surface of the second semiconductor chip **120** may contact the upper surface of the first semiconductor chip **110**. As a result, a joint gap might not be formed between the lower surface of the second semiconductor chip **120** and the upper surface of the first semiconductor chip **110**.

(26) When particles are present on the lower surface of the second semiconductor chip **120** in the hybrid bonding process for directly contacting the lower surface of the second semiconductor chip **120** with the upper surface of the first semiconductor chip **110**, a void may be generated between the first semiconductor chip **110** and the second semiconductor chip **120**. The void may bring about

an electrical connection error between the bonding pad **122** and the connection via **116**. For example, the particles may be generated in cutting a wafer including the second semiconductor chips **120** along a scribe lane. The particles may adhere to an edge portion of the second semiconductor chip **120** in a high concentration.

(27) To prevent the electrical connection error between the second semiconductor chip **120** and the first semiconductor chip **110** due to the particles, the second semiconductor chip **120** may have an area larger than an area of the bonding region B of the first semiconductor chip **110**. Thus, when the second semiconductor chip **120** may be disposed on the upper surface of the bonding region B of the first semiconductor chip **110**, the edge portion of the second semiconductor chip **120** may be horizontally protruded from the bonding region B. For example, an overhang **124** protruded from the bonding region B may be formed at the edge portion of the second semiconductor chip **120**. Because the second semiconductor chip **120** may have the rectangular shape, the overhang **124** may be formed at four side surfaces of the second semiconductor chip **120**.

(28) The overhang **124** may be positioned over the groove **112** at the peripheral region P of the first semiconductor chip **110**. Thus, the overhang **124** might not contact the upper surface of the peripheral region P. As a result, the overhang **124** may have a lower surface that is spaced apart from a bottom surface of the groove **112** to form a gap between the lower surface of the overhang **124** and the bottom surface of the groove **112**.

(29) As mentioned above, the particles generated in cutting the wafer may be adhered to the edge portion of the second semiconductor chip **120** in a high concentration. Thus, the particles may also be adhered to the lower surface of the overhang **124** corresponding to the edge portion of the second semiconductor chip **120** in a high concentration. However, the lower surface of the overhang **124** with the particles might not contact the upper surface of the first semiconductor chip **110**, for example, the bottom surface of the peripheral region P. As a result, the bonding pads **122** of the second semiconductor chip **120** may effectively contact the connection vias **116** in the bonding region B. For example, the particles on the overhang **124** may have no influence on the electrical connection between the bonding pads **122** of the second semiconductor chip **120** and the connection vias **116** in the bonding region B.

(30) In example embodiments of the present disclosure, when the second semiconductor chip **120** may have a width W of about 200 μm , the overhang **124** may have a horizontal length L of about 30 μm to about 90 μm . For example, the horizontal length L of the overhang **124** protruded from the bonding region B may be about 30 μm to about 90 μm . Here, the edge portion of the second semiconductor chip **120** may be partially damaged during the cutting process of the wafer. The damage may be mainly generated within a region having a length of about 30 μm measured from an outer side surface of the second semiconductor chip. The bonding pads **122** might not be disposed in the edge portion of the second semiconductor chip **120** with the damage. Thus, the horizontal length L of the overhang **124**, which might not be electrically connected to the first semiconductor chip **110**, may be no less than about 30 μm . However, when the damage may be mainly generated within a region having a length of below 30 μm measured from an outer side surface of the second semiconductor chip, the horizontal length L of the overhang **124** may also be below 30 μm .

(31) Further, when the horizontal length L of the overhang **124** may be above about 90 μm , the bonding region B of the second semiconductor chip **120** may have a small area. Thus, the maximum horizontal length L of the overhang **124** may be restricted to about 90 μm . As a result, the horizontal length L of the overhang **124** may be about 3/20 times to about 9/20 times the width W of the second semiconductor chip **120**.

(32) Further, to prevent the particles generated in cutting the wafer from being adhered to the lower surface of the overhang **124**, the depth D of the groove **112** may be no less than about 8 μm . Thus, a distance between the lower surface of the overhang **124** and the bottom surface of the groove **112** corresponding to the depth D of the groove **112** may also be no less than about 8 μm . A maximum

height of the scattered particles generated in cutting the wafer may be below about 8 μm . Thus, setting the distance between the bottom surface of the groove **112** and the lower surface of the overhang **124** may be no less than about 8 μm to decrease the concentration of particles on the lower surface of the overhang **124**.

(33) The molding member **150** may be formed on the upper surface of the first semiconductor chip **110** to surround the second semiconductor chip **120**. Because the second semiconductor chip **120** may contact the bonding region B of the first semiconductor chip **110**, only the upper surface of the peripheral region P, for example, only the bottom surface of the groove **112** may be exposed. Thus, the molding member **150** may be formed on the upper surface of the peripheral region P. For example, the molding member **150** may be formed in a space between the overhang **124** and the groove **112**. Alternatively, the molding member **150** might not be formed on the upper surface of the second semiconductor chip **120**. In this case, a heat spreader may be disposed on the exposed upper surface of the second semiconductor chip **120**. The molding member **150** may include an epoxy molding compound (EMC).

(34) The conductive bumps **160** may be mounted on the lower surface of the first semiconductor chip **110**, for example, the lower insulation layer **132**. The conductive bumps **160** may be electrically connected to the lower ends of the connection vias **116**. The conductive bumps **160** may include solder bumps.

(35) FIG. **3** is a plan view and FIGS. **4** to **8** are cross-sectional views illustrating a method of manufacturing the semiconductor package in FIG. **1**.

(36) Referring to FIG. **3**, the wafer may be cut along the scribe lane to separate the second semiconductor chips **120**.

(37) Each of the second semiconductor chips **120** in the wafer may also be divided into a bonding region B and a peripheral region P similarly to the first semiconductor chip **110**. The bonding region B may be a central portion of the second semiconductor chip **120**. The peripheral region P may be an edge portion of the second semiconductor chip **120** configured to surround the bonding region B.

(38) Conventionally, a cut line of the wafer may correspond to a side surface of the bonding region B. Thus, a conventional second semiconductor chip may have a size only including the bonding region B without the peripheral region P. For example, the conventional second semiconductor chip may have an area substantially the same as an area of the bonding region B of the first semiconductor chip **110**. Thus, the particles generated in the cutting process may be adhered to an edge portion of the conventional second semiconductor chip that only includes the bonding region B.

(39) In contrast, according to example embodiments of the present disclosure, a cut line of the wafer may be moved from the side surface of the bonding region B to an outside of the second semiconductor chip **120**. Thus, the second semiconductor chip **120** separated from the wafer may include the bonding region B and the peripheral region P configured to surround the bonding region B. As a result, the second semiconductor chip **120** may have an area larger than an area of the bonding region B of the first semiconductor chip **110**.

(40) The particles generated in cutting the wafer may be mainly adhered to the peripheral region P, e.g., a region between the side surface of the second semiconductor chip **120** and a dotted line I in FIG. **3**. In the second semiconductor chip **120** of FIG. **1**, the region between the side surface of the second semiconductor chip **120** and the dotted line I may correspond to the overhang **124**.

(41) Referring to FIG. **4**, the plurality of the first semiconductor chips **110** may be formed in a wafer **170**. Each of the first semiconductor chips **110** may include the connection vias **116**, a lower insulation layer **132** and the wiring **118**.

(42) The groove **112** may be formed at the upper surface of the wafer **170**. For example, the groove **112** may be formed at the upper surface of each of the peripheral regions P among the upper surfaces of the first semiconductor chips **110**. The depth D of the groove **112** may no less than

about 8 μm .

(43) In example embodiments of the present disclosure, the groove **112** may be formed along the whole peripheral region P. Thus, the groove **112** may have a width that is substantially the same as the width of the peripheral region P. The groove **112** may be formed by a laser cutting process, a half cutting process, etc. The groove **112** may have various shapes, and the present invention is not necessarily restricted to using grooves having a specific shape.

(44) Referring to FIG. 5, the upper insulation layer **130** may be formed on the upper surface of the first semiconductor chip **110**. For example, the upper insulation layer **130** may be formed on the upper surfaces of the peripheral region P and the bonding region B. Because the groove **112** may be formed in the peripheral region P, the upper insulation layer **130** may be formed along the inner surface of the groove **112**. The upper insulation layer **130** may be formed by a chemical vapor deposition (CVD) process, but the present invention is not necessarily limited thereto.

(45) The upper insulation layer **130** may be planarized to provide the upper insulation layer **130** with a uniform thickness. The upper insulation layer **130** may be planarized by a chemical mechanical polishing (CMP) process, but the present invention is not necessarily limited thereto.

(46) Referring to FIG. 6, the second semiconductor chip **120** may be bonded to the bonding region B of the first semiconductor chip **110** by the hybrid bonding process. Thus, the bonding pads **122** of the second semiconductor chip **120** may be directly bonded to the connection vias **116** in the bonding region B of the first semiconductor chip **110**.

(47) The hybrid bonding process may include a dangling process and an annealing process. In the dangling process, the lower surface of the second semiconductor chip **120** may contact the upper surface of the bonding region B in the first semiconductor chip **110** to generate a dangling bonding between silicon in the second semiconductor chip **120** and silicon in the first semiconductor chip **110**. In the annealing process, a heat may be applied to the second semiconductor chip **120** and the first semiconductor chip **110** to generate a covalent bonding between the bonding pad **122** and the connection via **116** by expanding the bonding pad **122** and the connection via **116**.

(48) As used herein, the generation of a dangling bonding between two objects is understood to be a bonding process in which dangling bonds are present. A dangling bond is an unsatisfied valence on an immobilized atom. An atom with a dangling bond is also referred to as an immobilized free radical or an immobilized radical, a reference to its structural and chemical similarity to a free radical. Some allotropes of silicon, such as amorphous silicon, display a high concentration of dangling bonds. In modern semiconductor device operation, hydrogen, oxygen or other such elements may be introduced to the silicon during the synthesis process to replace dangling bonds.

(49) After performing the hybrid bonding process on the second semiconductor chip **120** and the first semiconductor chip **110**, the overhang **124** of the second semiconductor chip **120** may be horizontally protruded from the bonding region B of the first semiconductor chip **110**. Further, the overhang **124** may be spaced apart from the peripheral region P by the groove **112**. Thus, the particles on the overhang **124** may have no influence on the electrical connection between the bonding pads **122** of the second semiconductor chip **120** and the connection vias **116** of the first semiconductor chip **110**.

(50) Referring to FIG. 7, the molding member **150** may be formed on the peripheral region P of the first semiconductor chip **110** to surround the second semiconductor chips **120** with the molding member **150**.

(51) Referring to FIG. 8, the first semiconductor chip **110** and the molding member **150** may then be cut along the cut line set in the peripheral regions P. Alternatively, after cutting the first semiconductor chip **110**, the molding member **150** may then be formed.

(52) The conductive bumps **160** may be mounted on the lower surface of the first semiconductor chip **110** to complete the semiconductor package **100** in FIG. 1.

(53) FIG. 9 is a cross-sectional view illustrating a semiconductor package in accordance with example embodiments of the present disclosure, and FIG. 10 is a cross-sectional view taken along a

line B-B' in FIG. 9;

(54) A semiconductor package **100a** of this example embodiment may include elements substantially the same as those of the semiconductor package **100** in FIG. 1 except for a groove. Thus, the same reference numerals may refer to the same elements and to the extent that detailed description of certain elements has been omitted, it may be assumed that those elements are at least similar to corresponding elements that have been described elsewhere in the present disclosure.

(55) Referring to FIGS. 9 and 10, a groove **112a** may be formed at a part of the peripheral region P of the first semiconductor chip **110**. Thus, the groove **112a** may have a bottom surface lower than the upper surface of the bonding region B of the first semiconductor chip **110**. In contrast, the upper surface of the peripheral region P at which the groove **112a** might not be formed may be substantially coplanar with the upper surface of the bonding region B. Thus, the groove **112a** may have a width narrower than the width of the peripheral region P. For example, the groove **112a** may have an inner surface corresponding to the outer side surface of the bonding region B. Therefore, the groove **112a** may have a shape configured to horizontally extend from the outer side surface of the bonding region B.

(56) The groove **112a** may be formed by partially removing the upper insulation layer **130** and the semiconductor chip **110** in the peripheral region P. Thus, the upper insulation layer **130** might not be present on the bottom surface of the groove **112a**. For example, the upper insulation layer **130** may be disposed on the upper surface of the bonding region B and a portion of the upper surface of the peripheral region P at which the groove **112a** might not be formed.

(57) Alternatively, the groove **112a** may be formed by wholly removing the upper insulation layer **130** and by partially removing the semiconductor chip **110** in the peripheral region P. In this case, the groove **112a** may have a width that is substantially the same as the width of the peripheral region P. However, the upper insulation layer **130** might not be present on the bottom surface of the groove **112a**.

(58) The overhang **124** of the second semiconductor chip **120** may be positioned over the groove **112a**. Thus, the overhang **124** may have a lower surface that is spaced apart from the upper surface of the peripheral region P, e.g., the bottom surface of the groove **112a**. As a result, as mentioned above, the bonding failure between the second semiconductor chip **120** and the first semiconductor chip **110** caused by the particles on the overhang **124** might not be generated.

(59) FIGS. 11 to 15 are cross-sectional views illustrating a method of manufacturing the semiconductor package in FIG. 9.

(60) Referring to FIG. 11, the plurality of the first semiconductor chips **110** may be formed in the wafer **170**. Each of the first semiconductor chips **110** may include the connection vias **116**, a lower insulation layer **132** and the wiring **118**.

(61) The upper insulation layer **130** may be formed on the upper surface of the wafer **170**. The upper insulation layer **130** may be formed by a chemical vapor deposition (CVD) process, but the present invention is not necessarily limited thereto.

(62) The upper insulation layer **130** may be planarized to provide the upper insulation layer **130** with a uniform thickness. The upper insulation layer **130** may be planarized by a chemical mechanical polishing (CMP) process, but the present invention is not necessarily limited thereto.

(63) Referring to FIG. 12, the groove **112a** may be formed at the upper surface of the wafer **170**. For example, the groove **112a** may be formed at the upper surface of each of the peripheral regions P among the upper surfaces of the first semiconductor chips **110**. For example, the upper insulation layer **130** and the first semiconductor chip **110** in the peripheral region P may be removed to form the groove **112a**. Thus, the upper insulation layer **130** might not be present on the inner surface of the groove **112a**. For example, the width of the groove **112a** may be narrower than the width of the peripheral region P. The inner surface of the groove **112a** may correspond to the outer side surface of the bonding region B. As a result, the groove **112a** may have a shape horizontally extended from the outer side surface of the bonding region B.

(64) Alternatively, the groove **112a** may be formed by wholly removing the upper insulation layer **130** and by partially removing the semiconductor chip **110** in the peripheral region P. In this case, the groove **112a** may have a width that is substantially the same as the width of the peripheral region P. However, the upper insulation layer **130** might not be present on the bottom surface of the groove **112a**.

(65) Referring to FIG. **13**, the second semiconductor chip **120** may be bonded to the bonding region B of the first semiconductor chip **110** by the hybrid bonding process. Thus, the bonding pads **122** of the second semiconductor chip **120** may be directly bonded to the connection vias **116** in the bonding region B of the first semiconductor chip **110**.

(66) After performing the hybrid bonding process on the second semiconductor chip **120** and the first semiconductor chip **110**, the overhang **124** of the second semiconductor chip **120** may be horizontally protruded from the bonding region B of the first semiconductor chip **110**. Further, the overhang **124** may be spaced apart from the peripheral region P by the groove **112a**. Thus, the particles on the overhang **124** may have no influence on the electrical connection between the bonding pads **122** of the second semiconductor chip **120** and the connection vias **116** of the first semiconductor chip **110**.

(67) Referring to FIG. **14**, the molding member **150** may be formed on the peripheral region P of the first semiconductor chip **110** to surround the second semiconductor chips **120** with the molding member **150**.

(68) Referring to FIG. **15**, the first semiconductor chip **110** and the molding member **150** may then be cut along the cut line set in the peripheral regions P. Alternatively, after cutting the first semiconductor chip **110**, the molding member **150** may then be formed.

(69) The conductive bumps **160** may be mounted on the lower surface of the first semiconductor chip **110** to complete the semiconductor package **100** in FIG. **9**.

(70) FIG. **16** is a cross-sectional view illustrating a semiconductor package in accordance with example embodiments of the present disclosure.

(71) Referring to FIG. **16**, a semiconductor package **300** of this example embodiment may correspond to a fan-out type semiconductor package. The semiconductor package **300** may include a lower redistribution (RDL) structure **200**, a frame **310**, a first semiconductor chip **110**, a second semiconductor chip **120**, a molding member **340**, an upper RDL structure and external terminals **280**.

(72) The lower RDL structure **200** may include a first insulation layer **210**, first RDLs **220**, a second insulation layer **230**, second RDLs **240**, a third insulation layer **250**, third RDLs **260** and a fourth insulation layer **270**.

(73) In example embodiments of the present disclosure, the first insulation layer **210**, the second insulation layer **230**, the third insulation layer **250** and the fourth insulation layer **270** may include photo imagable dielectrics (PID). Alternatively, the first insulation layer **210**, the second insulation layer **230**, the third insulation layer **250** and the fourth insulation layer **270** may include other insulation materials. Further, the first insulation layer **210**, the second insulation layer **230**, the third insulation layer **250** and the fourth insulation layer **270** may have substantially the same thickness as one another or they may have different thicknesses from one another.

(74) The first RDLs **220**, the second RDLs **240** and the third RDLs **260** may include metals such as copper, aluminum, etc., but the present invention is not necessarily restricted to these particular metals. Further, the first RDLs **220**, the second RDLs **240** and the third RDLs **260** may have substantially the same thickness as one another or may have different thicknesses from one another.

(75) Alternatively, the lower RDL structure **200** may include stacked three or at least five insulation layers, and RDLs interposed between the insulation layers.

(76) The first insulation layer **210** may include a plurality of first via holes **212**. The first via holes **212** may be vertically formed through the first insulation layer **210**. A lower solder resist pattern may be formed on a lower surface of the first insulation layer **210**. The external terminals **280** may

be mounted on the lower surface of the first insulation layer **210**.

(77) The first RDLs **220** may be disposed on an upper surface of the first insulation layer **210**. The first RDLs **220** may include first via contacts **222** configured to fill the first via holes **212**. The first via contacts **222** may be exposed through openings of the lower solder resist pattern. The external terminals **280** may be electrically connected to the exposed first via contacts **222**.

(78) The second insulation layer **230** may be disposed on an upper surface of the first insulation layer **210**. The second insulation layer **230** may include a plurality of second via holes **232**. The second via holes **232** may be vertically formed through the second insulation layer **230** to partially expose the first RDLs **220**.

(79) The second RDLs **240** may be disposed on an upper surface of the second insulation layer **230**. The second RDLs **240** may include second via contacts **242** configured to fill the second via holes **232**. Thus, the first RDLs **220** and the second RDLs **240** may be electrically connected to each other through the second via contacts **242**.

(80) The third insulation layer **250** may be disposed on an upper surface of the second insulation layer **230**. The third insulation layer **250** may include a plurality of third via holes **235**. The third via holes **252** may be vertically formed through the third insulation layer **250** to partially expose the second RDLs **240**.

(81) The third RDLs **260** may be disposed on an upper surface of the third insulation layer **250**. The third RDLs **260** may include third via contacts **262** configured to fill the third via holes **252**. Thus, the second RDLs **240** and the third RDLs **260** may be electrically connected to each other through the third via contacts **262**.

(82) The fourth insulation layer **270** may be disposed on an upper surface of the third insulation layer **250**. The fourth insulation layer **270** may be configured to surround the third RDLs **260**. Upper surfaces of the third RDLs **260** may be upwardly exposed by the fourth insulation layer **270**.

(83) The frame **310** may be disposed on the upper surface of the lower RDL structure **200**. The frame **310** may include an insulation substrate **320** and a middle RDL **330**. The insulation substrate **320** may include a cavity. The cavity may be formed through a central portion of the insulation substrate **320**. The middle RDL **330** may be formed in the insulation substrate **320**.

(84) The insulation substrate **320** may include a first insulation layer **322** and a second insulation layer **324**. The first insulation layer **322** may have an opening vertically formed therethrough. The second insulation layer **324** may be formed on an upper surface of the first insulation layer **322**. The second insulation layer **324** may have an opening vertically formed therethrough.

(85) The middle RDL **330** may include a first middle RDL pattern **332** and a second middle RDL pattern **334**. The first middle RDL pattern **332** may be formed on a lower surface of the first insulation layer **322**. The second middle RDL pattern **334** may be formed on the upper surface of the first insulation layer **322**. The opening of the first insulation layer **322** may be filled with a first contact **336**. Thus, the first middle RDL pattern **332** and the second middle RDL pattern **334** may be electrically connected to each other through the first contact **336**. The opening of the second insulation layer **324** may be filled with a second contact **338**. The second contact **338** may be electrically connected to the second middle RDL pattern **334**. An upper surface of the second contact **338** may be upwardly exposed.

(86) The first semiconductor chip **110** and the second semiconductor chip **120** may be disposed within the cavity of the insulation substrate **320**. The first semiconductor chip **110** and the second semiconductor chip **120** may have a structure substantially the same as the structure in FIG. **1**. Thus, to the extent that detailed description of certain elements has been omitted, it may be assumed that those elements are at least similar to corresponding elements that have been described elsewhere in the present disclosure and any further illustrations with respect to the first semiconductor chip **110** and the second semiconductor chip **120** may be omitted herein for brevity. For example, the second semiconductor chip **120** may have the overhang **124**. Alternatively, the first semiconductor chip **110** and the second semiconductor chip **120** may have a structure

substantially the same as the structure in FIG. 9.

(87) The molding member **340** may be configured to mold the first semiconductor chip **110** and the second semiconductor chip **120**. In example embodiments of the present disclosure, the molding member **340** may be formed on the upper surface of the insulation substrate **320** to fill spaces between the first and second semiconductor chips **110** and **120** and an inner surface of the cavity.

(88) The upper RDL structure may include an upper insulation layer **360** and an upper RDL **370**. The upper insulation layer **360** may be formed on an upper surface of the molding member **340**. In example embodiments of the present disclosure, the upper insulation layer **360** may include PID. Alternatively, the upper insulation layer **360** may include other insulation materials.

(89) The upper insulation layer **360** may include a first insulation layer **362** and a second insulation layer **364**. The first insulation layer **362** may be formed on the upper surface of the molding member **340**. The first insulation layer **362** may have an opening exposing the second middle RDL pattern **334**.

(90) The upper RDL **370** may be formed on an upper surface of the first insulation layer **362** to fill the opening. Thus, the upper RDL **370** may be electrically connected to the second middle RDL pattern **334**.

(91) The second insulation layer **364** may be formed on the upper surface of the first insulation layer **362**. The second insulation layer **364** may have an opening exposing the upper RDL **370**.

(92) Additionally, an upper semiconductor chip may be disposed on an upper surface of the second insulation layer **364**. Conductive bumps of the upper semiconductor chip may be disposed in the openings of the second insulation layer **364** to electrically connect the upper semiconductor chip with the upper RDL **370** via the conductive bumps.

(93) FIG. **17** is a cross-sectional view illustrating a semiconductor package in accordance with example embodiments of the present disclosure.

(94) A semiconductor package **400** of this example embodiment may include elements substantially the same as those of the semiconductor package **300** in FIG. **16** except for further including a second semiconductor package. Thus, to the extent that detailed description of certain elements has been omitted, it may be assumed that those elements are at least similar to corresponding elements that have been described elsewhere in the present disclosure.

(95) Referring to FIG. **17**, the semiconductor package **400** may include the second semiconductor package stacked on the semiconductor package **300** in FIG. **16**. For example, the semiconductor package **400** of this example embodiment may have a package-on-package (POP) structure.

(96) The second semiconductor package may include a first semiconductor chip **410**, a second semiconductor chip **420**, conductive bumps **430**, an underfilling layer **440** and a molding member **450**.

(97) The first semiconductor chip **410** may be electrically connected to the semiconductor package **300** in FIG. **16** via conductive bumps **460** such as solder balls. For example, the conductive bumps **460** may be mounted on the upper RDL **370** of the semiconductor package **300** in FIG. **16**. A lower surface of the first semiconductor chip **410** may be electrically connected to the upper RDL **370** of the semiconductor package **300** via the conductive bumps **460**.

(98) The first semiconductor chips **410** may include a plurality of lower pads **414** and a plurality of upper pads **412**. The lower pads **414** may be disposed on the lower surface of the first semiconductor chip **410**. The lower pads **414** may electrically contact the conductive bumps **460**. The upper pads **412** may be disposed on an upper surface of the first semiconductor chip **410**.

(99) The second semiconductor chip **420** may be disposed on an upper surface of the first semiconductor chip **410**. The second semiconductor chip **420** may include a plurality of pads **422**. The pads **422** may be disposed on a lower surface of the second semiconductor chip **420**.

(100) The conductive bumps **430** may be interposed between the first semiconductor chip **410** and the second semiconductor chip **420**. For example, the conductive bumps **430** may be configured to electrically connect the upper pads **412** of the first semiconductor chip **410** with the pads **422** of the

second semiconductor chip **420**.

(101) The underfilling layer **440** may be interposed between the first semiconductor chip **410** and the second semiconductor chip **420** to surround the conductive bumps **430**. The underfilling layer **440** may include an insulation material such as an epoxy resin.

(102) The molding member **450** may be formed on the upper surface of the first semiconductor chip **410** to cover the second semiconductor chip **420**. The molding member **450** may include an EMC.

(103) FIG. **18** is a cross-sectional view illustrating a semiconductor package in accordance with example embodiments of the present disclosure.

(104) Referring to FIG. **18**, a semiconductor package **500** of this example embodiment may correspond to a fan-out type wafer level package. Thus, the semiconductor package **500** of this example embodiment may include a lower RDL structure **200**, a first semiconductor chip **110**, a second semiconductor chip **120**, a molding member **520**, a connection via **510**, an upper RDL, an upper insulation layer **360** and external terminals **380**.

(105) In example embodiments of the present disclosure, the lower RDL structure **200** may have a structure substantially the same as the structure of the lower RDL structure **200** in FIG. **16**. Thus, to the extent that detailed description of certain elements has been omitted, it may be assumed that those elements are at least similar to corresponding elements that have been described elsewhere in the present disclosure and any further illustrations with respect to the lower RDL structure **200** may be omitted herein for brevity.

(106) Further, the first semiconductor chip **110** and the second semiconductor chip **120** may have a structure substantially the same as the structure in FIG. **1**. Thus, to the extent that detailed description of certain elements has been omitted, it may be assumed that those elements are at least similar to corresponding elements that have been described elsewhere in the present disclosure and any further illustrations with respect to the first semiconductor chip **110** and the second semiconductor chip **120** may be omitted herein for brevity. For example, the second semiconductor chip **120** may have the overhang **124**. Alternatively, the first semiconductor chip **110** and the second semiconductor chip **120** may have a structure substantially the same as the structure in FIG. **9**.

(107) The molding member **520** may be formed on the upper surface of the lower RDL structure **200** to surround the side surfaces of the first and second semiconductor chips **110** and **120**. The molding member **520** may be a part of the wafer.

(108) The connection via **510** may be vertically formed through the molding member **520**. A lower end of the connection via **510** may be electrically connected to the lower RDL structure **200**. For example, the lower end of the connection via **510** may be electrically connected to the first RDL **220**. The connection via **510** may include a metal such as copper.

(109) The upper insulation layer **360** and the upper RDL **370** may have a structure substantially the same as the structure in FIG. **16**. Thus, to the extent that detailed description of certain elements has been omitted, it may be assumed that those elements are at least similar to corresponding elements that have been described elsewhere in the present disclosure and any further illustrations with respect to the upper insulation layer **360** and the upper RDL **370** may be omitted herein for brevity. An upper end of the connection via **520** may be electrically connected to the upper RDL **370**.

(110) FIG. **19** is a cross-sectional view illustrating a semiconductor package in accordance with example embodiments of the present disclosure.

(111) Referring to FIG. **19**, a semiconductor package **600** of this example embodiment may include a three-dimensional (3D) stack type semiconductor package. Thus, the semiconductor package **600** may include a package substrate **610**, a logic chip **620**, at least one first semiconductor chip **630**, a plurality of second semiconductor chips **700**, a molding member **640** and external terminals **650**.

(112) The logic chip **620** may be disposed on an upper surface of the package substrate **610**. The

logic chip **620** may be electrically connected to the package substrate **610** via conductive bumps **660**. The logic chip **620** may have a first bonding region **B1**, a second bonding region **B2** and a peripheral region **P**. First connection vias **624** may be disposed in the first bonding region **B1**. Second connection vias **626** may be disposed in the second bonding region **B2**.

(113) A groove **622** may be formed at the peripheral region **P** of the logic chip **620**. Thus, the first and second bonding regions **B1** and **B2** may have an upper surface higher than an upper surface of the peripheral region **P**.

(114) The first semiconductor chip **630** may be disposed on the upper surface of the first bonding region **B1**. The first semiconductor chip **630** may include bonding pads **632** disposed on a lower surface of the first semiconductor chip **630**. The bonding pads **632** may be connected to the first connection vias **624** by a hybrid bonding process. The first semiconductor chip **630** may include an SRAM chip.

(115) The first semiconductor chip **630** may have an area larger than an area of the first bonding region **B1** of the logic chip **620**. Thus, the first semiconductor chip **630** may include a first overhang **634** horizontally protruded from the first bonding region **B1**. The first overhang **634** may be spaced apart from the peripheral region **P** of the logic chip **620**.

(116) The second semiconductor chips **700** may be stacked on the upper surface of the second bonding region **B2**. Each of the second semiconductor chips **700** may have an area larger than an area of the second bonding region **B2** of the logic chip **620**. Further, each of the second semiconductor chip **700** may have a bonding region and a peripheral region. The bonding region of the second semiconductor chip **700** may have an area substantially the same as the area of the second bonding region **B2**. The peripheral region of the second semiconductor chip **700** may be configured to surround the bonding region of the second semiconductor chip **700**. Thus, at least one of the second semiconductor chips **700** may include a second overhang horizontally protruded from the second bonding region **B2**. The second overhang may be spaced apart from the peripheral region **P**. In example embodiments of the present disclosure, the second semiconductor chips **700** may include high bandwidth memory (HBM) chips.

(117) In example embodiments of the present disclosure, the second semiconductor chips **700** may include a 2-1 semiconductor chip **710**, a 2-2 second semiconductor chip **720**, a 2-3 semiconductor chip **730** and a 2-4 semiconductor chip **740** sequentially stacked.

(118) The 2-1 semiconductor chip **710** may include 2-1 bonding pads **712** and 2-1 connection vias **716**. The 2-1 bonding pads **712** may be disposed on a lower surface of the 2-1 semiconductor chip **710**. The 2-1 connection vias **716** may be vertically extended through the 2-1 semiconductor chip **710** from the 2-1 bonding pads **712** to an upper surface of the 2-1 semiconductor chip **710**. The 2-1 bonding pads **712** may be electrically connected to the second connection vias **626** of the logic chip **620** by a hybrid bonding process.

(119) A groove may be formed at the peripheral region of the upper surface of the 2-1 semiconductor chip **710**. Thus, the bonding region of the 2-1 semiconductor chip **710** may have an upper surface higher than an upper surface of the peripheral region. The 2-1 connection vias **716** may be disposed in the bonding region of the 2-1 semiconductor chip **710**.

(120) As mentioned above, because an area of the 2-1 semiconductor chip **710** may be larger than the area of the second bonding region **B2** of the logic chip **620**, the 2-1 semiconductor chip **710** may include a 2-1 overhang **714** spaced apart from the peripheral region **B** of the logic chip **620**.

(121) The 2-2 semiconductor chip **720** may include 2-2 bonding pads **722** and 2-2 connection vias **726**. The 2-2 bonding pads **722** may be disposed on a lower surface of the 2-2 semiconductor chip **720**. The 2-2 connection vias **726** may be vertically extended through the 2-2 semiconductor chip **720** from the 2-2 bonding pads **722** to an upper surface of the 2-2 semiconductor chip **720**. The 2-2 bonding pads **722** may be electrically connected to the 2-1 connection vias **716** of the 2-1 semiconductor chip **710** by a hybrid bonding process.

(122) A groove may be formed at the peripheral region of the upper surface of the 2-2

semiconductor chip **720**. Thus, the bonding region of the 2-2 semiconductor chip **720** may have an upper surface higher than an upper surface of the peripheral region. The 2-2 connection vias **726** may be disposed in the bonding region of the 2-2 semiconductor chip **720**.

(123) As mentioned above, because an area of the 2-2 semiconductor chip **720** may be larger than the area of the bonding region of the 2-1 semiconductor chip **710**, the 2-2 semiconductor chip **720** may include a 2-2 overhang **724** spaced apart from the peripheral region of the 2-1 semiconductor chip **710**.

(124) The 2-3 semiconductor chip **730** may include 2-3 bonding pads **732** and 2-3 connection vias **736**. The 2-3 bonding pads **732** may be disposed on a lower surface of the 2-3 semiconductor chip **730**. The 2-3 connection vias **736** may be vertically extended through the 2-3 semiconductor chip **730** from the 2-3 bonding pads **732** to an upper surface of the 2-3 semiconductor chip **730**. The 2-3 bonding pads **732** may be electrically connected to the 2-2 connection vias **726** of the 2-2 semiconductor chip **720** by a hybrid bonding process.

(125) A groove may be formed at the peripheral region of the upper surface of the 2-3 semiconductor chip **730**. Thus, the bonding region of the 2-3 semiconductor chip **730** may have an upper surface higher than an upper surface of the peripheral region. The 2-3 connection vias **736** may be disposed in the bonding region of the 2-3 semiconductor chip **730**.

(126) As mentioned above, because an area of the 2-3 semiconductor chip **730** may be larger than the area of the bonding region of the 2-2 semiconductor chip **720**, the 2-3 semiconductor chip **730** may include a 2-3 overhang **734** spaced apart from the peripheral region of the 2-2 semiconductor chip **720**.

(127) The 2-4 semiconductor chip **740** may include 2-4 bonding pads **742**. The 2-4 bonding pads **742** may be disposed on a lower surface of the 2-4 semiconductor chip **740**. The 2-4 bonding pads **742** may be electrically connected to the 2-3 connection vias **736** of the 2-3 semiconductor chip **730** by a hybrid bonding process.

(128) As mentioned above, because an area of the 2-4 semiconductor chip **740** may be larger than the area of the bonding region of the 2-3 semiconductor chip **730**, the 2-4 semiconductor chip **740** may include a 2-4 overhang **744** spaced apart from the peripheral region of the 2-3 semiconductor chip **730**.

(129) The molding member **640** may be formed on the upper surface of the logic chip **620** to cover the first semiconductor chip **630** and the second semiconductor chips **700**. The molding member **640** may include an EMC.

(130) The external terminals **650** may be mounted on a lower surface of the package substrate **610**. The external terminals **650** may include solder balls.

(131) According to example embodiments of the present disclosure, the overhang may be formed at the edge portion of the second semiconductor chip by the groove at the peripheral region of the first semiconductor chip. The overhang may be spaced apart from the peripheral region of the first semiconductor chip. Thus, the edge portion of the second semiconductor chip with the overhang might not contact the first semiconductor chip. As a result, a bonding failure, which may be caused by particles generated in a cutting the wafer and adhered to the edge portion of the second semiconductor chip, between the first semiconductor chip and the second semiconductor chip might not be generated.

(132) The foregoing is illustrative of example embodiments of the present disclosure and is not to be construed as limiting thereof. Although a few example embodiments of the present disclosure have been described, those skilled in the art will readily appreciate that many modifications are possible without materially departing from the novel teachings and aspects of the present invention. Accordingly, all such modifications are intended to be included within the scope of the present invention.

Claims

1. A method of manufacturing a semiconductor package, the method comprising: forming upwardly protruding peripheral regions on an upper surface of a wafer, the wafer including a plurality of first semiconductor chips; forming bonding regions on the upper surface of the wafer by forming a groove at the upwardly protruding peripheral regions; hybrid-bonding a plurality of second semiconductor chips, each of which has an area larger than an area of each of the bonding regions, to the bonding regions to form an overhang at an edge portion of each of the second semiconductor chips, the overhang spaced apart from a bottom surface of the groove; and cutting the wafer along the peripheral regions.
2. The method of claim 1, wherein the overhang protrudes from the bonding regions and comes to an end overlapping the groove in a vertical direction.
3. The method of claim 1, wherein forming the groove comprises forming the groove along the whole peripheral region to provide the groove with a width substantially the same as a width of the peripheral region.
4. The method of claim 1, wherein forming the groove comprises forming the groove at a part of the peripheral region to provide the groove with a width narrower than a width of the peripheral region.
5. The method of claim 4, wherein the groove is extended from a side surface of the bonding region.
6. The method of claim 1, further comprising forming an upper insulation layer on the bottom surface of the groove and an upper surface of the bonding region.
7. The method of claim 6, further comprising planarizing the upper insulation layer.
8. The method of claim 1, further comprising forming an upper insulation layer on an upper surface of the first semiconductor chip, before forming the groove at the peripheral region.
9. The method of claim 8, further comprising planarizing the upper insulation layer.
10. The method of claim 1, wherein hybrid-bonding the second semiconductor chip to the bonding region comprises: generating a dangling bonding between the second semiconductor chip and the bonding region; and annealing the second semiconductor chip and the bonding region to covalent bond a bonding pad of the second semiconductor chip to an upper pad of the bonding region.
11. The method of claim 1, further comprising forming a molding member on an upper surface of the first semiconductor chip, the molding member at least partially surrounding the second semiconductor chip.
12. The method of claim 11, wherein the forming of the molding member comprises filling a space between the overhang and the peripheral region with the molding member.
13. The method of claim 1, further comprising mounting conductive bumps on a lower surface of the first semiconductor chip.
14. A method of manufacturing a semiconductor package, the method comprising: forming upwardly protruding peripheral regions on an upper surface of a wafer, the wafer including a plurality of first semiconductor chips; forming bonding regions on the upper surface of the wafer by forming a groove at the upwardly protruding peripheral regions; hybrid-bonding a plurality of second semiconductor chips, each of which has an area larger than an area of each of the bonding regions, to the bonding regions to form an overhang at an edge portion of each of the second semiconductor chips, the overhang spaced apart from a bottom surface of the groove; and cutting the wafer along the peripheral regions, wherein the overhang protrudes from the bonding regions and comes to an end overlapping the groove in a vertical direction, and wherein forming the groove comprises forming the groove along the whole peripheral region to provide the groove with a width substantially the same as a width of the peripheral region.
15. The method of claim 14, further comprising forming an upper insulation layer on the bottom

surface of the groove and an upper surface of the bonding region.

16. The method of claim 14, further comprising forming an upper insulation layer on an upper surface of the first semiconductor chip, before forming the groove at the peripheral region.

17. The method of claim 14, further comprising forming a molding member on an upper surface of the first semiconductor chip, the molding member at least partially surrounding the second semiconductor chip.

18. A method of manufacturing a semiconductor package, the method comprising: forming upwardly protruding peripheral regions on an upper surface of a wafer, the wafer including a plurality of first semiconductor chips; forming bonding regions on the upper surface of the wafer by forming a groove at the upwardly protruding peripheral regions; hybrid-bonding a plurality of second semiconductor chips, each of which has an area larger than an area of each of the bonding regions, to the bonding regions to form an overhang at an edge portion of each of the second semiconductor chips, the overhang spaced apart from a bottom surface of the groove; and cutting the wafer along the peripheral regions, wherein the overhang protrudes from the bonding regions and comes to an end overlapping the groove in a vertical direction, and wherein forming the groove comprises forming the groove at a part of the peripheral region to provide the groove with a width narrower than a width of the peripheral region.

19. The method of claim 18, further comprising forming an upper insulation layer on the bottom surface of the groove and an upper surface of the bonding region.

20. The method of claim 19, wherein forming the groove comprises partially removing the upper insulation layer and the first semiconductor chip in the peripheral region.
