



US012405532B2

(12) **United States Patent**
Kang et al.

(10) **Patent No.:** **US 12,405,532 B2**
(45) **Date of Patent:** **Sep. 2, 2025**

(54) **POLYMER AND COMPOSITION FOR FORMING AN ANTI-REFLECTIVE FILM AND METHOD OF MANUFACTURING AN INTEGRATED CIRCUIT DEVICE USING THE ANTI-REFLECTIVE FILM**

FOREIGN PATENT DOCUMENTS

CN 1637027 7/2005
JP 2003-119193 4/2003

(Continued)

(71) Applicant: **SAMSUNG ELECTRONICS CO., LTD.**, Suwon-Si (KR)

OTHER PUBLICATIONS

Machine English translation of WO 02/086624; Mizusawa et al. (Year: 2002).*

Chinese Office Action issued in corresponding CN Patent Application No. 202010005831.3 on Mar. 22, 2023.

Korean Office Action issued in corresponding KR Patent Application No. 10-2019-0036211 on Feb. 29, 2024.

Notice of Allowance issued in corresponding KR Patent Application No. 10-2019-0036211 on Nov. 27, 2024.

(Continued)

(72) Inventors: **Miyeong Kang**, Suwon-si (KR);
Sukwoo Hong, Suwon-si (KR);
Hyereun Kim, Suwon-si (KR); **Jihyun Kim**, Hwaseong-si (KR); **Hyunjin Kim**, Hwaseong-si (KR); **Hyojung Roh**, Hwaseong-si (KR); **Jongkyoung Park**, Hwaseong-si (KR); **Jungyoul Lee**, Hwaseong-si (KR)

(73) Assignee: **SAMSUNG ELECTRONICS CO., LTD.**, Suwon-si (KR)

Primary Examiner — Jessica M Roswell

(74) Attorney, Agent, or Firm — MORGAN, LEWIS & BOCKIUS LLP

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(57) **ABSTRACT**

A polymer having a repeating unit represented by Formula 1:

(21) Appl. No.: **18/133,166**

(22) Filed: **Apr. 11, 2023**

(65) **Prior Publication Data**

US 2023/0244146 A1 Aug. 3, 2023

Related U.S. Application Data

(63) Continuation of application No. 16/695,569, filed on Nov. 26, 2019, now Pat. No. 11,650,502.

(30) **Foreign Application Priority Data**

Mar. 28, 2019 (KR) 10-2019-0036211

(51) **Int. Cl.**
G03F 7/09 (2006.01)
C08G 18/38 (2006.01)

(Continued)

(52) **U.S. Cl.**
CPC **G03F 7/091** (2013.01); **C08G 18/3802** (2013.01); **C08G 18/3819** (2013.01);
(Continued)

(58) **Field of Classification Search**

CPC G03F 7/091; G03F 7/038; G03F 7/039; G03F 7/11; G03F 7/20; G03F 7/26; G03F 7/322; C08G 18/3802; C08G 18/3819; C08G 18/792; C08G 71/04; C08G 73/0644; C08G 73/0655; C09D 175/04; C09D 5/006; C09D 179/04; H01L 21/027
See application file for complete search history.


(56) **References Cited**

U.S. PATENT DOCUMENTS

8,039,202 B2 10/2011 Sui et al.
8,344,088 B2 1/2013 Kennedy et al.

(Continued)

[Formula 1]



wherein each of R₁, R₂, and R₃ is independently selected from a substituted or unsubstituted C1-C6 chain-like saturated or unsaturated hydrocarbon group having 0 to 2 first heteroatoms or a substituted or unsubstituted C3-C6 cyclic saturated or unsaturated hydrocarbon group having 0 to 2 first heteroatoms, wherein at least one of R₁, R₂, and R₃ is a hydrocarbon group substituted with a fluorine atom. R₄ is a C1-C10 chain-like saturated or unsaturated hydrocarbon group having 0 to 2 second heteroatoms or a C3-C10 cyclic saturated or unsaturated hydrocarbon group having 0 to 2 second heteroatoms. R₅ is a C1-C10 chain-like saturated or unsaturated hydrocarbon group having 1 to 6 third heteroatoms or a C3-C10 cyclic saturated or unsaturated hydrocarbon group having 1 to 6 third heteroatoms.

US 12,405,532 B2

Page 2

- (51) **Int. Cl.** 2004/0110096 A1 * 6/2004 Kishioka C08G 18/791
C08G 18/79 (2006.01) 430/313
C09D 175/04 (2006.01) 2007/0298349 A1 12/2007 Zhang et al.
G03F 7/038 (2006.01) 2013/0236833 A1 9/2013 Houlihan et al.
G03F 7/039 (2006.01) 2017/0351178 A1 12/2017 Roh et al.
2020/0310249 A1 10/2020 Kang et al.
- (52) **U.S. Cl.**
CPC **C08G 18/792** (2013.01); **C09D 175/04**
(2013.01); **G03F 7/038** (2013.01); **G03F**
7/039 (2013.01)
- (56) **References Cited**
- U.S. PATENT DOCUMENTS
- | | | |
|---------------|---------|---------------------|
| 8,383,318 B2 | 2/2013 | Meador et al. |
| 8,557,877 B2 | 10/2013 | Mukhopadhyay et al. |
| 9,651,867 B2 | 5/2017 | Han et al. |
| 10,134,606 B2 | 11/2018 | Woo et al. |
- FOREIGN PATENT DOCUMENTS
- | | | |
|----|-------------------|---------|
| JP | 2005-250434 | 9/2005 |
| JP | 2011-236154 | 11/2011 |
| JP | 2012-518812 | 8/2012 |
| KR | 10-2014-0034504 | 3/2014 |
| KR | 10-2015-0133550 | 11/2015 |
| KR | 10-2017-0136189 | 12/2017 |
| KR | 10-2018-0133230 | 12/2018 |
| WO | WO 02/086624 A1 * | 12/2002 |
| WO | 2012-033004 | 3/2012 |
- G03F 7/11
- * cited by examiner

FIG. 1




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E




FIG. 2F




FIG. 2G




FIG. 3





FIG. 4



1

POLYMER AND COMPOSITION FOR FORMING AN ANTI-REFLECTIVE FILM AND METHOD OF MANUFACTURING AN INTEGRATED CIRCUIT DEVICE USING THE ANTI-REFLECTIVE FILM

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of U.S. patent application Ser. No. 16/695,569 filed on Nov. 26, 2019, which claims priority under 35 U.S.C. § 119 to Korean Patent Application No. 10-2019-0036211, filed on Mar. 28, 2019, in the Korean Intellectual Property Office, the disclosures of which are incorporated by reference in their entireties.

1. TECHNICAL FIELD

The present inventive concept relates to a polymer and composition used in a process of manufacturing an integrated circuit (IC) device and a method of manufacturing an IC device, and more particularly, to a polymer and composition for forming an anti-reflective film for a photolithography process and a method of manufacturing an IC device using the anti-reflective film.

2. DISCUSSION OF RELATED ART

Significant progress has been made with respect to down-scaling IC devices and increasing the integration density of the IC devices which has resulted in the formation of IC devices having reduced design rules. New techniques for improving a dimensional precision have been required for patterns for implementing unit devices having fine critical dimensions (CDs). For example, it has become necessary to develop processes for preventing defects or deterioration of a process distribution due to undesired photoresist residue that may remain in an exposure area during a photolithography process.

SUMMARY


The present inventive concepts provide a polymer having a structure that may prevent undesired photoresist residue from being left in an exposure area during a photolithography process to prevent the occurrence of defects or degradation of a process distribution.

The present inventive concepts also provide a composition for forming an anti-reflective film including a polymer that may prevent undesired photoresist residue from being left in an exposure area during a photolithography process to prevent the occurrence of defects or degradation of a process distribution.

Furthermore, the present inventive concepts provide a method of manufacturing an integrated circuit (IC) device, which may prevent undesired photoresist residue from being left in an exposure area during a photolithography process to prevent occurrence of defects or degradation of a process distribution.

According to an aspect of the present inventive concepts, there is provided a polymer having a repeating unit represented by Formula 1:

2



wherein each of R₁, R₂, and R₃ is independently selected from a substituted or unsubstituted C1-C6 chain-like saturated or unsaturated hydrocarbon group having 0 to 2 first heteroatoms or a substituted or unsubstituted C3-C6 cyclic saturated or unsaturated hydrocarbon group having 0 to 2 first heteroatoms, wherein at least one of R₁, R₂, and R₃ is a hydrocarbon group substituted with a fluorine atom. R₄ is a C1-C10 chain-like saturated or unsaturated hydrocarbon group having 0 to 2 second heteroatoms or a C3-C10 cyclic saturated or unsaturated hydrocarbon group having 0 to 2 second heteroatoms. R₅ is a C1-C10 chain-like saturated or unsaturated hydrocarbon group having 1 to 6 third heteroatoms or a C3-C10 cyclic saturated or unsaturated hydrocarbon group having 1 to 6 third heteroatoms.


According to another aspect of the present inventive concepts, there is provided a composition for forming an anti-reflective film, which includes a polymer having a repeating unit represented by Formula 1 and an organic solvent.

According to another aspect of the present inventive concept, there is provided a method of manufacturing an IC device. The method includes forming an anti-reflective film on a feature layer using a composition including a polymer having a repeating unit represented by Formula 1 and an organic solvent. A photoresist film is formed on the anti-reflective film. A first resist region of the photoresist film, which covers a first local region of the anti-reflective film, is exposed to light. The photoresist film is developed using a development agent to remove the exposed first resist region and to form a photoresist pattern. The developing of the photoresist film increases the hydrophilicity of a top surface of the first local region of the anti-reflective film.

According to another aspect of the present inventive concepts, there is provided a method of manufacturing an IC device. The method includes forming an anti-reflective film on a feature layer using a composition including a polymer having a repeating unit represented by Formula 1 and an organic solvent. The anti-reflective film includes a top surface having a first contact angle to deionized water (DIW). A photoresist film is formed to cover the top surface of the anti-reflective film. A partial region of the photoresist film is exposed to light. The photoresist film is developed using a development agent to form a photoresist pattern. The developing of the photoresist film increases the hydrophilicity of a top surface of a local region of the anti-reflective film that is not covered by the photoresist pattern.

According to another aspect of the present inventive concepts, there is provided a method of manufacturing an IC device. The method includes forming an anti-reflective film on a feature layer using a composition including an isocyanurate polymer including at least one fluorine-containing substituent. A photoresist film is formed to cover the anti-

5




wherein * denotes a bonding position (e.g., a binding site to a neighboring atom).

In some exemplary embodiments, in Formula 1, R_4 may serve as a chromophore to absorb light.

The third heteroatom that may be contained in R_5 may be at least one selected from an oxygen atom O and a nitrogen atom N.

The first heteroatom, the second heteroatom and the third heteroatom may be the same as each other. Alternatively, one or more of the first heteroatom, the second heteroatom and the third heteroatom may be different from each other.

In some embodiments, R_5 may be selected from among the following structures:



wherein * denotes a bonding position (e.g., a binding site to a neighboring atom).

The polymer having the repeating unit represented by Formula 1 may have a weight-average molecular weight Mw of about 1,000 to about 100,000. In an example, the weight-average molecular weight Mw of the polymer may range from about 2,000 to about 50,000. In another example, the weight-average molecular weight Mw of the polymer may range from about 2,000 to about 10,000. When the weight-average molecular weight Mw of the polymer is less than about 1,000, it may be difficult to obtain a coating film having a uniform thickness during a process of coating an underlying structure (e.g., a substrate) with a composition including the polymer to form the anti-reflective film. When the weight-average molecular weight Mw of the polymer exceeds 100,000, the solubility of the polymer in an organic solvent may be excessively reduced. Therefore, it may be difficult to apply the polymer to the process of coating an underlying structure.

A composition for forming an anti-reflective film according to exemplary embodiments may include a polymer having a repeating unit represented by Formula 1 and an organic solvent.


In the composition, the polymer having the repeating unit represented by Formula 1 may be contained at a content of about 0.01 to 10% by weight, based on the total weight of the composition. In some exemplary embodiments, the amount of the organic solvent in the composition may be adjusted such that the content of solids including the polymer having the repeating unit represented by Formula 1 in the composition ranges from 0.01 to 10% by weight.

The organic solvent may include cyclohexanone, cyclopentanone, butyrolactone, dimethylacetamide, dimethylformamide, dimethylsulfoxide, N-methyl pyrrolidone (NMP),

6

tetrahydrofurfural alcohol, propylene glycol monomethyl ether (PGME), propylene glycol monomethyl ether acetate (PGMEA), ethyl lactate, or a combination thereof. However, exemplary embodiments of the present inventive concepts are not limited thereto and the organic solvent may be various other compositions.

In some exemplary embodiments, a composition for forming an anti-reflective film may further include a polymer having a repeating unit represented by Formula 2:




[Formula 2]

wherein R_6 is a C6-C12 saturated or unsaturated hydrocarbon group having 0 to 2 fourth heteroatoms.

In some exemplary embodiments, R_6 may serve as a chromophore to absorb light.

In some exemplary embodiments, R_6 may be a C6-C12 saturated or unsaturated hydrocarbon group having 0 to 2 oxygen atoms O. For example, R_6 may be any one selected from the following structures:



wherein * denotes a bonding position (e.g., a binding site to a neighboring atom).

When a composition for forming an anti-reflective film according to exemplary embodiments includes the polymer having the repeating unit represented by Formula 1 and the polymer having the repeating unit represented by Formula 2, a total content of the polymers in the composition may range from 0.01 to 10% by weight, based on the total weight of the composition.

In some exemplary embodiments, the composition for forming the anti-reflective film may further include at least one of a crosslinking agent and an acid generator.

The crosslinking agent may induce the cross-linking of the polymer included in the composition and cure the cross-linked polymer.

In some exemplary embodiments, the crosslinking agent may include a C_4 to C_{50} hydrocarbon compound. For example, the crosslinking agent may include a resin containing melamines, methylols, glycolurils, polymeric glycolurils, benzoguanamine, urea, a resin containing hydroxyalkylamide, epoxy and epoxy amine resins, blocked isocyanates, or divinyl monomers. In some other exemplary embodiments, the crosslinking agent may include fluorine-containing or fluorine-free organic alcohols or epoxide substituents. In some other exemplary embodiments, a commercially available crosslinking agent may be used as the crosslinking agent, such as PL 1174 (Cytec Industries Inc., located in West Paterson, N.J.). However, exemplary embodiments of the present inventive concepts are not limited thereto and the crosslinking agent may be various other compositions.

The content of the crosslinking agent may range from about 0.01 to about 5% by weight, based on the total weight of the composition. For example, the content of the crosslinking agent may be about 0.05 to about 2% by weight. When the content of the crosslinking agent is less than 0.01% by weight, even if the underlying structure (e.g., the substrate) is coated with the composition and a bake process is performed to form the anti-reflective film using the composition, a crosslinking reaction may not be accurately achieved. Therefore, a sufficient crosslinking ratio required to form the anti-reflective film may not be obtained, and the anti-reflective film may exhibit a thickness loss. When the content of the crosslinking agent exceeds about 5% by weight, outgassing may occur due to the sublimation of an unreacted crosslinking agent, which remains after the anti-reflective film is formed. The outgassing may result in contamination of the underlying structure and apparatuses.

The acid generator may promote a crosslinking reaction of the polymers included in the composition. The acid generator may be a thermal acid generator (TAG). In some exemplary embodiments, the TAG may include a sulfonium salt compound, an iodonium salt compound, an amine salt compound, or a combination thereof. For example, the TAG may include triphenylsulfonium nonaflate, dodecylbenzenesulfonic acid, paratoluenesulfonic acid, pyridinium nonaflate, or a combination thereof. However, exemplary embodiments of the present inventive concepts are not limited thereto and the acid generator may be various other compounds.

The content of the acid generator may range from about 0.001 to about 0.5% by weight, based on the total weight of the composition. For example, the content of the acid generator may range from about 0.1 to about 0.3% by weight. When the content of the acid generator is less than about 0.001% by weight, the amount of the acid required for the crosslinking reaction may be insufficient. Therefore, the crosslinking reaction may not be completed in the resultant anti-reflective film. When the content of the acid generator exceeds about 0.5% by weight, the process stability may deteriorate due to an excessive acid catalyst.

The content of the organic solvent in the composition may correspond to the remaining content of the composition excluding the contents of the polymers included in the composition and additives, such as the crosslinking agent and the acid generator.

Hereinafter, a method of manufacturing an IC device, according to exemplary embodiments of the present inventive concepts, will be described.

FIG. 1 is a flowchart of a method of manufacturing an IC device, according to an exemplary embodiment of the present inventive concepts.

FIGS. 2A to 2G are cross-sectional views illustrating process operations of a method of manufacturing an IC device, according to exemplary embodiments of the present inventive concepts.

Referring to FIGS. 1 and 2A, in process P10, an anti-reflective film 120 may be formed on a feature layer 110 using a composition including a polymer having a repeating unit represented by Formula 1.

In some exemplary embodiments, the polymer included in the composition may include only a polymer having the repeating unit represented by Formula 1. In some other exemplary embodiments, the polymer included in the composition may include the polymer having the repeating unit represented by Formula 1 and a polymer having a repeating unit represented by Formula 2.

In some exemplary embodiments, the anti-reflective film 120 may include a resultant product of a crosslinking reaction of the polymer having the repeating unit represented by Formula 1. In some other exemplary embodiments, the anti-reflective film 120 may include a resultant product of a crosslinking reaction of the polymer having the repeating unit represented by Formula 1 and the polymer having the repeating unit represented by Formula 2.

In some exemplary embodiments, the feature layer 110 may include a semiconductor substrate. For example, the feature layer 110 may include a semiconductor, such as silicon (Si) or germanium (Ge), or a compound semiconductor, such as silicon germanium (SiGe), silicon carbide (SiC), gallium arsenide (GaAs), indium arsenide (InAs), indium phosphide (InP), etc. In some other exemplary embodiments, the feature layer 110 may include an insulating film or a conductive film. For example, the feature layer 110 may include a metal, an alloy, a metal carbide, a metal nitride, a metal oxynitride, a metal oxycarbide, a semiconductor, polysilicon, oxide, nitride, oxynitride, or a combination thereof. However, exemplary embodiments of the present inventive concepts are not limited thereto and the feature layer may include various other compounds.

The anti-reflective film 120 may control the irregular reflection of light from a light source that is used during an exposure process for manufacturing the IC device. In some exemplary embodiments, the anti-reflective film 120 may absorb light reflected by the feature layer 110 located thereunder. The anti-reflective film may include one or more chromophores for absorption of light.

In some exemplary embodiments, the formation of the anti-reflective film 120 may include coating the feature layer 110 with a composition for forming an anti-reflective film according to embodiments and annealing the coated composition to induce a crosslinking reaction of polymers included in the composition. The process of annealing the composition may be performed at a temperature of about 150° C. to about 400° C. for about 10 seconds to about 100 seconds. However, exemplary embodiments of the present inventive concepts are not limited thereto. During the annealing of the composition, the polymers included in the composition may be cured due to a crosslinking agent. In some exemplary embodiments, the anti-reflective film 120 may be formed to a thickness of about 20 nm to about 100 nm. However, the thickness of the anti-reflective film 120 is not limited thereto. For example, in some exemplary embodiments the thickness of the anti-reflective film may be less than 20 nm or greater than 100 nm.

In some exemplary embodiments, the composition may include a polymer having a repeating unit represented by Formula 1 and an organic solvent. In some other exemplary embodiments, the composition may include a polymer having a repeating unit represented by both Formula 1 and Formula 2. In yet some other exemplary embodiments, the composition may further include at least one of a crosslinking agent and an acid generator. Detailed descriptions of the polymer having the repeating unit represented by Formula 1, the polymer having the repeating unit represented by Formula 2, the crosslinking agent, and the acid generator may be understood with reference to the above descriptions.

After the anti-reflective film 120 is formed, substituents of the polymer having the repeating unit represented by Formula 1 may be exposed on a top surface 120T of the anti-reflective film 120. The substituents exposed on the top surface 120T of the anti-reflective film 120 may include at least one of R₁, R₂, and R₃. At least one of R₁, R₂, and R₃ may be a hydrocarbon group substituted with a fluorine

atom. Accordingly, hydrocarbon groups substituted with fluorine atoms may be exposed on the top surface **120T** of the anti-reflective film **120**.

Referring to FIGS. **1** and **2B**, in process **P20**, a photoresist film **130** may be formed on the anti-reflective film **120** formed in process **P10**. For example, as shown in the exemplary embodiment of FIG. **2B**, the photoresist film **130** may be formed directly on the anti-reflective film **120**.

In some exemplary embodiments, the photoresist film **130** may include a positive-type photoresist. The photoresist film **130** may include a resin having a polarity that is increased by an action of an acid. For example, the photoresist film **130** may include a resin containing an acid-decomposable group and a chemical-amplification-type photoresist including a photoacid generator (PAG). The photoresist film **130** may include 248-nm KrF excimer laser resist, 193-nm ArF excimer laser resist, 157-nm F2 excimer laser resist, or 13.5-nm extreme ultraviolet (EUV) resist. The photoresist film **130** may be formed using a spin coating process.

In an exemplary embodiment, the photoresist film **130** is formed by coating the anti-reflective film **120** with a photoresist composition and the photoresist composition is then annealed. The process of annealing the photoresist composition may be performed at a temperature of about 100° C. to about 150° C. for about 10 seconds to about 100 seconds. However, exemplary embodiments of the present inventive concepts are not limited thereto and the photoresist may be formed on the anti-reflective film **120** by other processes or by a coating and annealing process performed at different temperatures and/or time periods. Furthermore, a negative-type photomask may be used in other exemplary embodiments.

A thickness of the photoresist film **130** may be several tens to several hundred times greater than a thickness of the anti-reflective film **120**. For example, in some embodiments, the photoresist film **130** may be formed to a thickness of about 1 μm to about 6 μm. However, the thickness of the photoresist film **130** is not limited thereto.

Referring to FIGS. **1** and **2C**, in process **P30**, a first resist region **130A** of the photoresist film **130**, which covers a first local region **120A** of the anti-reflective film **120**, may be exposed to light applied during the photolithography process.

A second resist region **130B** of the photoresist film **130** may be a non-exposure area. The first local region **120A** of the anti-reflective film **120** may be covered by the exposed first resist region **130A**, while a second local region **120B** may be covered by the second resist region **130B**, which is the non-exposure area.

A photomask **140** may be used to expose the first resist region **130A** of the photoresist film **130**. The photomask **140** may include a plurality of light-shielding areas **LS** and a plurality of light-transmitting areas **LT**. To expose the photoresist film **130**, the photomask **140** may be aligned in a predetermined position on the feature layer **110**, and the first resist region **130A** of the photoresist film **130** may be exposed to light through the plurality of light-transmitting areas **LT** of the photomask **140**.

The photomask **140** may include a transparent substrate **142** and a plurality of light-shielding patterns **144** formed on the transparent substrate **142**. As shown in FIG. **2C**, the light-shielding patterns may be disposed on a surface of the transparent substrate **142** that faces the feature layer **110**. In an exemplary embodiment, the transparent substrate **142** may include quartz. In an exemplary embodiment, the plurality of light-shielding patterns **144** may include chromium (Cr). The plurality of light-shielding patterns **144** may

constitute a plurality of light-shielding areas **LS**. A plurality of light-transmitting areas **LT** may be defined by the plurality of light-shielding patterns **144**.

Radiations having various wavelengths may be used to expose the first resist region **130A** of the photoresist film **130**. For example, the exposure process may be performed using an i-line (365-nm), 248-nm, 193-nm, extreme ultraviolet (EUV) (13.5-nm), or 157-nm exposure wavelength. In some exemplary embodiments, an immersion lithography process may be performed when the 193-nm exposure wavelength is used to expose the first resist region. In embodiments in which the immersion lithography process is used, a topcoat layer may be further formed to cover the photoresist film **130** before the exposure process to prevent a direct contact of an immersion liquid with the photoresist film **130** and to prevent components of the photoresist film **130** from immersing in the immersion liquid. In some other exemplary embodiments, even if the immersion lithography process is used, a fluorine-containing additive may be added to the photoresist film **130** and the topcoat layer may be omitted.

In the first resist region **130A** of the photoresist film **130**, an acid-decomposable group may be deprotected due to an acid, which is generated from the PAG due to the exposure process, and a polarity of the first resist region **130A** may be larger than in other portions of the photoresist film **130**.

Referring to FIGS. **1** and **2D**, in process **P40**, the photoresist film **130** (refer to FIG. **2C**) may be developed using a development agent **150** to remove the exposed first resist region **130A**. The hydrophilicity of a top surface **120AT** of the first local region of the anti-reflective film **120** may be increased using the development agent **150**.

As shown in FIG. **2D**, when the photoresist film **130** (refer to FIG. **2C**) is developed using the development agent **150**, the exposed first resist region **130A** may be removed from the photoresist film **130** to form a photoresist pattern **130P**. The photoresist pattern **130P** may include the second resist region **130B** (refer to FIG. **2C**) of the photoresist film **130**.

The development agent **150** may include a basic aqueous solution (e.g., a solution having a pH greater than 7.0). For example, in an exemplary embodiment, the development agent **150** may include a tetramethyl ammonium hydroxide (TMAH) aqueous solution. The TMAH aqueous solution may have a concentration of about 2 to about 5% by weight. For example, to develop the photoresist pattern **130P**, the exposed photoresist film **130** shown in FIG. **2C** may be developed for about 10 seconds to about 100 seconds using the TMAH aqueous solution.

While the photoresist pattern **130P** is being formed by developing the photoresist film **130** using the development agent **150**, the exposed first resist region **130A** may be removed so that the top surface **120AT** of the first local region **120A** of the anti-reflective film **120** may be exposed to the development agent **150**. A hydrocarbon group that is substituted with a fluorine atom included in at least one of R1, R2, and R3 included in the polymer having the repeating unit represented by Formula 1 may be exposed on the top surface **120AT** of the first local region **120A**. When the top surface **120AT** of the first local region **120A** of the anti-reflective film **120** is exposed to the development agent **150**, the hydrocarbon group that is substituted with the fluorine atom included in at least one of R1, R2, and R3 may be dissolved due to a chemical reaction with the development agent **150** and deprotected from the polymer. As a result, the hydrophilicity of the top surface **120AT** of the first local region **120A** may be increased.

11

As the hydrophilicity of the top surface **120AT** of the first local region **120A** increases, a contact angle of the top surface **120AT** of the first local region **120A** to deionized water (DIW) may be less than before the development process described with reference to process **P40** of FIG. 1 and FIG. 2D is performed.

In some exemplary embodiments, after the anti-reflective film **120** is formed as described with reference to process **P10** of FIG. 1 and FIG. 2A, the top surface **120AT** of the anti-reflective film **120** has a first contact angle to DIW. After the top surface **120AT** of the first local region **120A** of the anti-reflective film **120** undergoes a chemical reaction with the development agent **150** during the development process described with reference to process **P40** of FIG. 1 and FIG. 2D, the top surface may have a second contact angle to DIW. The second contact angle may be less than the first contact angle. In some exemplary embodiments, the second contact angle may be at least 4 degrees (°) less than the first contact angle. In some other exemplary embodiments, the second contact angle may be at least 9° less than the first contact angle.

In some exemplary embodiments, the top surface **120AT** of the first local region **120A** of the anti-reflective film **120** which undergoes a chemical reaction with the development agent **150** as described with reference to process **P40** of FIG. 1 and FIG. 2D, may have a smaller contact angle to DIW than the contact angle of a top surface **120BT** of the second local region **120B** of the anti-reflective film **120** which is covered by the photoresist pattern **130P** and does not undergo a chemical reaction with the development agent. For example, the top surface **120BT** of the second local region **120B** may have a third contact angle to DIW after the photoresist film **130** is developed as described with reference to process **P40** of FIG. 1 and FIG. 2D. The top surface **120AT** of the first local region **120A** may have a second contact angle to DIW, and the second contact angle may be less than the third contact angle. In some exemplary embodiments, the second contact angle may be at least 4° less than the third contact angle. In some other exemplary embodiments, the second contact angle may be at least 9° less than the third contact angle.

As the contact angle of the top surface **120AT** of the first local region **120A** of the anti-reflective film **120** to DIW is reduced and the hydrophilicity of the top surface **120AT** of the first local region **120A** increases after the photoresist film **130** is developed, a residue of the exposed first resist region **130A** of the photoresist film **130** may be cleanly removed in process **P40** without remaining on the top surface **120AT** of the first local region **120A** of the anti-reflective film **120**. Accordingly, after the process of developing the photoresist film **130**, problems caused by photoresist residue remaining on the top surface **120AT** of the first local region **120A** of the anti-reflective film **120** may be prevented.

According to exemplary embodiments, the anti-reflective film **120** may be formed using the composition including the polymer having the repeating unit represented by Formula 1. While the hydrocarbon group, which is substituted with the fluorine atom included in at least one of R1, R2, and R3, is dissolved due to a chemical reaction with the development agent **150** and deprotected from the polymer on the top surface **120AT** of the first local region **120A**, since the polymers included in the anti-reflective film **120** are cross-linked and form a matrix structure that is insoluble to the development agent **150**, a substantial variation in the thickness of the anti-reflective film **120** may not be affected. Accordingly, the thickness of the first local region **120A** of the anti-reflective film **120** may not exhibit a substantial

12

change before and after the process of developing the photoresist film **130** using the development agent **150**. For example, the reduction of the thickness of the first local region **120A** of the anti-reflective film after the process of developing the photoresist film is performed may be no greater than 10-25 Å. Accordingly, as described with reference to process of FIG. 1 and FIG. 2D, the thickness of the first local region **120A** of the anti-reflective film **120**, which undergoes a chemical reaction with the development agent **150** during process **P40** may be substantially equal to a thickness of the second local region **120B**.

Referring to FIGS. 1 and 2E, in process **P50**, the first local region **120A** (refer to FIG. 2D) of the anti-reflective film **120** may be anisotropically etched to form an anti-reflective pattern **120P** in the second local region **120B**. The anti-reflective pattern may be disposed below (e.g., covered by) the photoresist pattern **130P**.

In embodiments in which a portion of the anti-reflective film **120** may be dissolved by the development agent **150** and the thickness of the anti-reflective film **120** is reduced after the process of developing the photoresist film **130** is performed, the thickness of the anti-reflective film **120** may not be uniform depending on a position of the anti-reflective film **120** on the feature layer **110**. In these embodiments, when exposed portions of the anti-reflective film **120** are etched during a subsequent process, a process distribution may be degraded due to the non-uniform thickness of the anti-reflective film **120**. This may adversely affect a profile of the anti-reflective pattern **120P**, which is obtained after the etching of the anti-reflective film **120**. Furthermore, after the developed portions of the anti-reflective film **120** are etched, a film-quality distribution or thickness distribution of underlying structures may be degraded.

However, in the method of manufacturing the IC, according to the exemplary embodiments of the present inventive concepts, when the photoresist film **130** is developed using the development agent **150** as described with reference to process **P40** of FIG. 1 and FIG. 2D, when the anti-reflective film **120** undergoes a chemical reaction with the development agent **150**, there may be no substantial loss of thickness of the anti-reflective film **120**. Accordingly, the anti-reflective pattern **120P**, which is obtained as a result of the etching of the anti-reflective film **120**, may have a desired vertical profile. Therefore, when the feature layer **110** is processed using the anti-reflective pattern **120P** during a subsequent process, a desired critical dimension may be precisely controlled in a processing region of the feature layer **110**.

After the anti-reflective pattern **120P** is formed, a plurality of openings **160** may be formed in the anti-reflective pattern **120P** and a photoresist pattern **130P** to expose a portion of the feature layer **110**.

Referring to FIG. 1, in process **P60**, the feature layer **110**, which is exposed through the plurality of openings **160**, may be processed using the anti-reflective pattern **120P** and the photoresist pattern **130P** as a mask pattern.

For example, the process of processing the feature layer **110** may include various processes, such as a process of implanting impurity ions into the feature layer **110** through the plurality of openings **160**, a process of etching the feature layer **110** through the plurality of openings **160**, a process of forming an additional film on the feature layer **110** through the plurality of openings **160**, a process of modifying a portion of the feature layer **110** through the plurality of openings **160**, etc.

In the exemplary embodiment shown in FIG. 2F, an ion implantation process is performed as an example process of processing the feature layer **110** exposed through the plu-

13

ality of openings 160. However, exemplary embodiments of the present inventive concepts are not limited thereto. As shown in FIG. 2F, impurity ions 170 may be implanted into the feature layer 110 through the plurality of openings 160, thereby forming a plurality of wells 172 in the feature layer 110. For example, the plurality of wells may extend into the thickness of the feature layer 110. Each of the plurality of wells 172 may include an impurity region into which the impurity ions 170 are implanted. The impurity ions 170 may be an n-type dopant or a p-type dopant. In embodiments in which the feature layer 110 includes a Group-IV semiconductor substrate (e.g., a Si substrate), the n-type dopant may include a Group-V element, such as phosphorus (P), arsenic (As), and antimony (Sb), and the p-type dopant may include a Group-III element, such as boron (B). However, exemplary embodiments of the present inventive concepts are not limited to the above-described examples, and the impurity ions 170 may be variously modified according to a material of the feature layer 110.

Referring to FIG. 2G, the anti-reflective pattern 120P and the photoresist pattern 130P that remains on the feature layer 110 after the processing of the feature layer in process P60 is performed may be subsequently removed. For example, an ashing process and a strip process may be used to remove the anti-reflective pattern 120P and the photoresist pattern 130P. However, exemplary embodiments of the present inventive concepts are not limited thereto and the anti-reflective pattern 120P and photoresist pattern 130P may be removed by various other methods known in the art.

In the method of manufacturing the IC device, according to the exemplary embodiments described with reference to FIGS. 1 and 2A to 2G, when the first local region 120A (refer to FIGS. 2D-2E) of the anti-reflective film 120 is anisotropically etched to form the anti-reflective pattern 120P, the anisotropic etching process may be performed without a process variation relative to a position of the anti-reflective film 120 on the feature layer 110. Therefore, when the feature layer 110 is processed using the anti-reflective pattern 120P and the photoresist pattern 130P, critical dimensions of processing regions or patterns to be formed may be precisely controlled to improve a dimensional precision.

FIG. 3 is a flowchart of a method of manufacturing an IC device, according to an exemplary embodiment of the present inventive concepts.

The method of manufacturing the IC device, according to exemplary embodiments of the present inventive concepts, will be described with reference to FIGS. 2A to 2G and 3.

Referring to FIGS. 2A and 3, in process P210, an anti-reflective film 120 may be formed on a feature layer 110 using a composition including a polymer having a repeating unit represented by Formula 1 using the same method as that described in process P10 of FIG. 1.

In an exemplary embodiment, the top surface 120T of the anti-reflective film 120 may have a first contact angle of about 50° to 75° to DIW.

Referring to FIGS. 2B and 3, in process P220, a photoresist film 130 may be formed on the anti-reflective film 120 using the same method as that described in process P20 of FIG. 1.

Referring to FIGS. 2C and 3, in process P230, a partial region of the photoresist film 130 comprising the first resist region 130A may be exposed to light using the same method as that described in process P30 of FIG. 1.

Referring to FIGS. 2D and 3, in process P240, by performing the same method as that described in process P40 of FIG. 1, the photoresist film 130 (refer to FIG. 2C) is developed using the development agent 150 to form the

14

photoresist pattern 130P, and the hydrophilicity of the top surface 120AT of the first local region 120A of the anti-reflective film 120, which is not covered by the photoresist pattern 130P, may be increased using the development agent 150.

As the hydrophilicity of the top surface 120AT of the first local region 120A increases, a contact angle of the top surface 120AT of the first local region 120A to DIW may be reduced. In some exemplary embodiments, the top surface 120AT of the first local region 120A may have a second contact angle to DIW that is at least 4° less than the first contact angle. In another exemplary embodiment, the second contact angle to DIW may be at least 9° less than the first contact angle. For instance, in an exemplary embodiment, the second contact angle may range from about 40° to about 65°. However, exemplary embodiments of the present inventive concepts are not limited thereto.

Referring to FIGS. 2E and 3, in process P250, the first local region 120A (refer to FIG. 2D) of the anti-reflective film 120 may be anisotropically etched using the same method as that described in process P50 of FIG. 1, thereby forming an anti-reflective pattern 120P.

Referring to FIG. 3, in process P260, the feature layer 110, which is exposed by a plurality of openings 160, may be processed using the anti-reflective pattern 120P and the photoresist pattern 130P as a mask pattern in the same manner as that described in process P60 of FIG. 1. H

In some exemplary embodiments, an ion implantation process described with reference to FIG. 2F may be performed to process the feature layer 110 exposed through the plurality of openings 160. However, in other exemplary embodiments, various processes, such as a process of etching at least a portion of the feature layer 110, a process of forming an additional film on the feature layer 110 through the plurality of openings 160, and a process of modifying a portion of the feature layer 110 through the plurality of openings 160, may be performed to process the feature layer 110 exposed through the plurality of openings 160.

Thereafter, the anti-reflective pattern 120P and the photoresist pattern 130P remaining on the feature layer 110 may be removed in a similar manner to that described with reference to FIG. 2G.

In the method of manufacturing the IC device, according to the exemplary embodiments described with reference to FIGS. 2A to 2G and 3, when the feature layer 110 is processed using the anti-reflective pattern 120P and the photoresist pattern 130P, CDs of processing regions or patterns to be formed may be precisely controlled to improve a dimensional precision.

FIG. 4 is a flowchart of a method of manufacturing an IC device, according to an exemplary embodiment of the present inventive concepts.

A method of manufacturing the IC device, according to exemplary embodiments of the present inventive concepts, will be described with reference to FIGS. 2A to 2G and 4.

Referring to FIGS. 2A and 4, in process P310, an anti-reflective film 120 may be formed on a feature layer 110 using a composition including an isocyanurate polymer containing at least one fluorine-containing substituent.

The isocyanurate polymer may have a repeating unit represented by Formula 1. The at least one fluorine-containing substituent may include at least one of R₁, R₂, and R₃ of Formula 1. The anti-reflective film 120 may be formed on the feature layer 110 using the same method as that described in process P10 of FIG. 1.

15

Referring to FIGS. 2B and 4, in process P320, a photoresist film 130 may be formed to cover the anti-reflective film 120, using the same method as that described in process P20 of FIG. 1.

Referring to FIGS. 2C and 4, in process P330, a first resist region 130A of the photoresist film 130 may be exposed to light using the same method as that described in process P30 of FIG. 1.

Referring to FIGS. 2D and 4, in process P340, the photoresist film 130 (refer to FIG. 2C) may be developed using a development agent 150 in the same manner as that described in process P40 of FIG. 1 to form a photoresist pattern 130P. The hydrophilicity of a top surface of the first local region 120A of the anti-reflective film 120 which is exposed to the light in process P330 is increased by undergoing a chemical reaction with the development agent 150.

As the hydrophilicity of the top surface 120AT of the first local region 120A increases, a contact angle of the top surface 120AT of the first local region 120A to DIW may be reduced. The reduced contact angle permits a residue of the first resist region to be clearly removed from the top surface 120AT of the first local region 120A.


Thereafter, at least some of the processes described with reference to processes P50 and P60 of FIG. 1 and FIGS. 2E to 2G may be performed as necessary.

In the method of manufacturing the IC device, according to the exemplary embodiments of FIGS. 2A to 2G and 4, CDs of processing regions or patterns to be formed by processing the feature layer 110 may be precisely controlled to improve a dimensional precision.

Hereinafter, examples of synthesis of polymers according to exemplary embodiments and examples of preparation and evaluation of compositions according to exemplary embodiments will be described. However, the exemplary embodiments of the present inventive concepts are not limited by the following descriptions of Examples of synthesis, Examples of preparation, and Evaluation Examples.

Example 1-1: Synthesis of Polymer 1A

Polymer 1A is a polymer of Formula 1, in which each of R_1 , R_2 , and R_3 is $-\text{CH}_2\text{CF}_3$, R_4 is an ethyl group ($-\text{C}_2\text{H}_5$), and R_5 is represented by Formula 3-1:



wherein * is a bonding position (e.g., a binding site to a neighboring atom).

52.5 g of tris(1,3-oxathiolane-2-thion-5-ylmethyl)isocyanurate, 8.9 g of propylamine, 14.8 g of 1,2-bis(2-aminoethoxy)ethane, and 228 g of dimethylformamide were placed in a reactor and stirred at a temperature of about 85° C. for about 15 hours. Thereafter, a temperature of the reactor was lowered to room temperature of about 25° C., and 48.5 g of 3,3,3-trifluoropropionyl chloride was slowly added dropwise to the obtained reaction solution and further reacted at a room temperature of about 25° C. for about 10 hours. Afterwards, 45 g of an ion exchange resin (Amberlite A21) was added to the obtained solution, and the reaction solution was stirred at room temperature for about 1 hour. The reaction solution was then filtered and added dropwise to normal heptane to obtain a precipitate. The precipitate was dried to obtain the polymer 1A. The obtained polymer 1A

16

had a weight-average molecular weight Mw of about 2560 and a polydispersity index (PDI) of 1.56.

Example 1-2: Synthesis of Polymer 1B

Polymer 1B is a polymer of Formula 1 in which each of R_1 , R_2 , and R_3 is $-\text{CF}_2\text{CF}_3$, R_4 is an ethyl group ($-\text{C}_2\text{H}_5$), and R_5 is represented by Formula 3-1

The polymer 1B was obtained using the same method as in Example 1-1 except that 102.3 g of pentafluoropropionic anhydride was used instead of 48.5 g of 3,3,3-trifluoropropionyl chloride. The obtained polymer 1B had a weight-average molecular weight Mw of about 2540 and a PDI of 1.54.

Example 1-3: Synthesis of Polymer 1C

Polymer 1C is a polymer of Formula 1 in which each of R_1 , R_2 , and R_3 is $-\text{CF}_2\text{CF}_2\text{CF}_3$, R_4 is an ethyl group ($-\text{C}_2\text{H}_5$), and R_5 is represented by Formula 3-1

The polymer 1C was obtained using the same method as in Example 1-1 except that 135.3 g of heptafluoropropionic anhydride was used instead of 48.5 g of 3,3,3-trifluoropropionyl chloride. The obtained polymer 1C had a weight-average molecular weight Mw of about 2620 and a PDI of 1.65.

Example 1-4: Synthesis of Polymer 1D

Polymer 1D is a polymer of Formula 1 in which R_1 is $-\text{OC}(\text{CH}_3)_3$, each of R_2 and R_3 is $-\text{CF}_3$, R_4 is an ethyl group ($-\text{C}_2\text{H}_5$), and R_5 is represented by Formula 3-1 in Formula 1.

The polymer 1D was obtained using the same method as in Example 1-1 except that 22.4 g of trifluoroacetic chloride and 46.5 g of tert-butoxycarbonyl (BOC) anhydride were used instead of 48.5 g of 3,3,3-trifluoropropionyl chloride. The obtained polymer 1D had a weight-average molecular weight Mw of about 2720 and a PDI of 1.68.

Example 1-5: Synthesis of Polymer 1E

Polymer 1E is a polymer of Formula 1, in which each of R_1 , R_2 , and R_3 is $-\text{OCH}_2\text{CF}_3$, R_4 is an ethyl group ($-\text{C}_2\text{H}_5$), and R_5 is represented by Formula 3-1

The polymer 1E was obtained using the same method as in Example 1-1 except that 82.5 g of 3,3,3-trifluoropropionic anhydride was used instead of 48.5 g of 3,3,3-trifluoropropionyl chloride. The obtained polymer 1E had a weight-average molecular weight Mw of about 2540 and a PDI of 1.51.

Example 1-6: Synthesis of Polymer 1F

Polymer 1F is a polymer of Formula 1 in which each of R_1 , R_2 , and R_3 is $-\text{CH}_2\text{CF}_3$, R_4 is a pentyl group ($-\text{C}_5\text{H}_{11}$), and R_5 is represented by Formula 3-1.

The polymer 1F was obtained using the same method as in Example 1-1 except that 15.2 g of hexylamine was used instead of 8.9 g of propylamine. The obtained polymer 1F had a weight-average molecular weight Mw of about 2190 and a PDI of 1.59.

Example 1-7: Synthesis of Polymer 1G


Polymer 1G is a polymer of Formula 1, in which each of R_1 , R_2 , and R_3 is $-\text{CH}_2\text{CF}_3$, R_4 is an ethoxymethyl group ($-\text{CH}_2\text{OC}_2\text{H}_5$), and R_5 is represented by Formula 3-1

17

The polymer 1G was obtained using the same method as in Example 1-1 except that 13.4 g of 2-ethoxyethylamine was used instead of 8.9 g of propylamine. The obtained polymer 1G had a weight-average molecular weight Mw of about 2230 and a PDI of 1.54.

Example 1-8: Synthesis of Polymer 1H

Polymer 1H is a polymer of Formula 1 in which each of R₁, R₂, and R₃ is —CH₂CF₃, R₄ is an ethyl group (—C₂H₅), and R₅ is represented by Formula 3-2:



wherein * denotes a bonding position (e.g., a binding site to a neighboring atom).

18

As a Comparative Example, a comparative composition was prepared that includes polyhydroxy styrene (PHS), which is one of the polymers having the repeating unit represented by Formula 2. The Comparative Example does not include a polymer having the repeating unit represented by Formula 1.

In each of Examples 2-1 to 2-8 and the Comparative Example, PL 1174 (Cytec Industries Inc., located in West Paterson, N.J.) was used as a crosslinking agent, pyridinium nonaflate was used as an acid generator, and a mixed solution PGMEA/PGME in which propylene glycol monomethyl ether acetate (PGMEA) and propylene glycol monomethyl ether (PGME) were mixed in a weight ratio of 7:3 was used as an organic solvent.

Detailed compositions of the example compositions for forming the anti-reflective films, which were obtained in Examples 2-1 to 2-8, and the comparative composition are shown in Table 1.

TABLE 1

	First polymer (content)	Second polymer (content)	Crosslinking agent (content)	Acid generator (content)	Solvent (content)
Example 2-1	Polymer 1A (0.6 wt %)	PHS (2.4 wt %)	PL 1174 (0.2 wt %)	Pyridinium nonaflate (0.1 wt %)	PGMEA/PGME (96.7 wt %)
Example 2-2	Polymer 1B (0.6 wt %)	PHS (2.4 wt %)	PL 1174 (0.2 wt %)	Pyridinium nonaflate (0.1 wt %)	PGMEA/PGME (96.7 wt %)
Example 2-3	Polymer 1C (0.6 wt %)	PHS (2.4 wt %)	PL 1174 (0.2 wt %)	Pyridinium nonaflate (0.1 wt %)	PGMEA/PGME (96.7 wt %)
Example 2-4	Polymer 1D (0.6 wt %)	PHS (2.4 wt %)	PL 1174 (0.2 wt %)	Pyridinium nonaflate (0.1 wt %)	PGMEA/PGME (96.7 wt %)
Example 2-5	Polymer 1E (0.6 wt %)	PHS (2.4 wt %)	PL 1174 (0.2 wt %)	Pyridinium nonaflate (0.1 wt %)	PGMEA/PGME (96.7 wt %)
Example 2-6	Polymer 1F (0.6 wt %)	PHS (2.4 wt %)	PL 1174 (0.2 wt %)	Pyridinium nonaflate (0.1 wt %)	PGMEA/PGME (96.7 wt %)
Example 2-7	Polymer 1G (0.6 wt %)	PHS (2.4 wt %)	PL 1174 (0.2 wt %)	Pyridinium nonaflate (0.1 wt %)	PGMEA/PGME (96.7 wt %)
Example 2-8	Polymer 1H (0.6 wt %)	PHS (2.4 wt %)	PL 1174 (0.2 wt %)	Pyridinium nonaflate (0.1 wt %)	PGMEA/PGME (96.7 wt %)
Comparative Example		PHS (3.0 wt %)	PL 1174 (0.2 wt %)	Pyridinium nonaflate (0.1 wt %)	PGMEA/PGME (96.7 wt %)

The polymer 1H was obtained using the same method as in Example 1-1 except that 19.2 g of 1,2-tris (2-aminoethoxy) ethane was used instead of 14.8 g of 1,2-bis (2-aminoethoxy) ethane. The obtained polymer 1H had a weight-average molecular weight Mw of about 3210 and a PDI of 1.78.

Examples 2-1 to 2-8; Manufacture of Composition for Forming Anti-Reflective Film

Compositions for forming anti-reflective films were prepared using polymer 1A to polymer 1H, which were obtained in Examples 1-1 to 1-8, respectively.

Evaluation Examples 1-1 to 1-8: Evaluation of Characteristics of Anti-Reflective Film

The compositions for forming the anti-reflective films obtained in Examples 2-1 to 2-8 were spin-coated on a silicon wafer and baked at a temperature of about 205° C. for 60 seconds to form anti-reflective films having a thickness of about 250 Å.

Refractive indices and extinction coefficients (k values) of anti-reflective films formed in Evaluation Examples 1-1 to 1-8 were measured using an ellipsometer (VUV-303, manufactured by J. A. Woolam).

Furthermore, each of the anti-reflective films formed in Evaluation Examples 1-1 to 1-8 was subjected to a bulk exposure process using an argon fluoride (ArF) exposure

developing the photoresist film using a development agent to remove the exposed first resist region and to form a photoresist pattern, wherein the developing of the photoresist film increases a hydrophilicity of a top surface of the first local region of the anti-reflective film.

21

2. The method of claim 1, wherein the increase of the hydrophilicity of the top surface of the first local region of the anti-reflective film is performed by a chemical reaction of the at least one of R_1 , R_2 , and R_3 that is the hydrocarbon group that is substituted with the at least one fluorine atom with the development agent.

3. The method of claim 1, wherein the development agent comprises a basic aqueous solution.

4. The method of claim 1, wherein

the top surface of the first local region of the anti-reflective film has a first contact angle to deionized water before the photoresist film is developed, and the top surface of the first local region of the anti-reflective film has a second contact angle to deionized water after the photoresist film is developed, wherein the second contact angle is less than the first contact angle.

5. The method of claim 4, wherein the second contact angle is at least 4° less than the first contact angle.

6. The method of claim 4, wherein the second contact angle is at least 9° less than the first contact angle.


7. The method of claim 1, wherein,

after the photoresist film is developed, a top surface of a second local region of the anti-reflective film, which is covered by the photoresist pattern, has a third contact angle to deionized water, and

the top surface of the first local region of the anti-reflective film has a second contact angle to deionized water, wherein the second contact angle is less than the third contact angle.

8. The method of claim 7, wherein, after the photoresist film is developed, a difference between a thickness of the first local region of the anti-reflective film and a thickness of the second local region of the anti-reflective film is in a range of 10-25 Å.

9. The method of claim 1, wherein, the composition for forming the anti-reflective film on the feature layer further comprises a polymer having a repeating unit represented by Formula 2:



[Formula 2]

wherein R_6 is a C6-C12 saturated or unsaturated hydrocarbon group having 0 to 2 fourth heteroatoms.

10. The method of claim 1, wherein, the composition for forming the anti-reflective film on the feature layer further comprises at least one of a crosslinking agent and an acid generator.

11. The method of claim 1, wherein the forming of the anti-reflective film comprises:

coating the composition on the feature layer; and annealing the coated composition.

12. The method of claim 1, further comprising:

anisotropically etching the first local region of the anti-reflective film to form an anti-reflective pattern after developing the photoresist film.

13. The method of claim 12, further comprising:


processing the feature layer that is exposed through the anti-reflective pattern using the anti-reflective pattern and the photoresist pattern as a mask pattern.

14. A method of manufacturing an integrated circuit device, the method comprising:

22

forming an anti-reflective film on a feature layer using a composition comprising a polymer and an organic solvent, wherein the anti-reflective film includes a top surface having a first contact angle to deionized water, and the polymer has a repeating unit represented by Formula 1:

[Formula 1]



wherein each of R_1 , R_2 , and R_3 is independently selected from $-\text{CH}_2\text{CF}_3$, $-\text{OC}(\text{CH}_3)_3$, $-\text{OCH}_2\text{CF}_3$, $-\text{OCF}_3$, or $-\text{OCF}_2\text{CF}_3$, wherein at least one of R_1 , R_2 , and R_3 is a hydrocarbon group that is substituted with at least one fluorine atom,

R_4 is a C1-C10 saturated or unsaturated hydrocarbon group having 0 to 2 second heteroatoms or a C3-C10 cyclic saturated or unsaturated hydrocarbon group having 0 to 2 second heteroatoms, and

R_5 is a C1-C10 saturated or unsaturated hydrocarbon group having 1 to 6 third heteroatoms or a C3-C10 cyclic saturated or unsaturated hydrocarbon group having 1 to 6 third heteroatoms;

forming a photoresist film that covers the top surface of the anti-reflective film;

exposing a partial region of the photoresist film to light; developing the photoresist film using a development agent to form a photoresist pattern, wherein the developing of the photoresist film increases a hydrophilicity of a top surface of a local region of the anti-reflective film that is not covered by the photoresist pattern.

15. The method of claim 14, wherein the increase of the hydrophilicity of the top surface of the local region of the anti-reflective film is performed by a chemical reaction of the at least one of R_1 , R_2 , and R_3 that is the hydrocarbon group that is substituted with the at least one fluorine atom with the development agent.

16. The method of claim 14, wherein, after the increase of the hydrophilicity of the top surface of the local region of the anti-reflective film, the top surface of the local region has a second contact angle to deionized water, wherein the second contact angle is at least 4° less than the first contact angle.


17. A method of manufacturing an integrated circuit device, the method comprising:

forming an anti-reflective film on a feature layer using a composition comprising an isocyanurate polymer including at least one fluorine-containing substituent; forming a photoresist film to cover the anti-reflective film; exposing a first resist region of the photoresist film to light, the first resist region covering a local region of the anti-reflective film; and

developing the photoresist film using a development agent to remove the exposed first resist region and to

23

increase a hydrophilicity of a top surface of the local region of the anti-reflective film,
 wherein the isocyanurate polymer has a repeating unit represented by Formula 1:



wherein each of R_1 , R_2 , and R_3 is independently selected from $-\text{CH}_2\text{CF}_3$, $-\text{OC}(\text{CH}_3)_3$, $-\text{OCH}_2\text{CF}_3$, $-\text{OCF}_3$, or $-\text{OCF}_2\text{CF}_3$, and at least one of R_1 , R_2 , and R_3 is the

24

hydrocarbon group substituted with at least one fluorine atom that comprises the fluorine-containing substituent,

R_4 is a C1-C10 saturated or unsaturated hydrocarbon group having 0 to 2 second heteroatoms or a C3-C10 cyclic saturated or unsaturated hydrocarbon group having 0 to 2 second heteroatoms, and

R_5 is a C1-C10 saturated or unsaturated hydrocarbon group having one to six third heteroatoms or a C3-C10 cyclic saturated or unsaturated hydrocarbon group having one to six third heteroatoms.

18. The method of claim 17, wherein the increase of the hydrophilicity of the top surface of the local region of the anti-reflective film is performed using a chemical reaction of the at least one fluorine-containing substituent that is exposed to the top surface of the local region with the development agent.

19. The method of claim 17, wherein

the top surface of the local region of the anti-reflective film has a first contact angle to deionized water before the photoresist film is developed and has a second contact angle after the photoresist film is developed, wherein the second contact angle is at least 4° less than the first contact angle.

* * * * *