

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12406843
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Harada; Kazuhiro et al.

Method of manufacturing semiconductor device, method of processing substrate, substrate processing apparatus, and recording medium

Abstract

There is included (a) loading a substrate where a conductive metal-element-containing film is exposed on a surface of the substrate into a process chamber under a first temperature; (b) supplying a reducing gas to the substrate while raising a temperature of the substrate to a second temperature higher than the first temperature in the process chamber; (c) forming a first film on the metal-element-containing film, by supplying a first process gas, which does not include an oxidizing gas, to the substrate under the second temperature in the process chamber; and (d) forming a second film on the first film such that the second film is thicker than the first film, by supplying a second process gas, which includes an oxidizing gas, to the substrate under a third temperature higher than the first temperature in the process chamber.

Inventors: Harada; Kazuhiro (Toyama, JP), Minami; Masayoshi (Toyama, JP), Kogura; Shintaro (Toyama, JP), Otani; Shogo (Toyama, JP), Hashimoto; Yoshitomo (Toyama, JP)

Applicant: Kokusai Electric Corporation (Tokyo, JP)

Family ID: 72338435

Assignee: Kokusai Electric Corporation (Tokyo, JP)

Appl. No.: 18/473625

Filed: September 25, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20240014032 A1	Jan. 11, 2024

Related U.S. Application Data

Publication Classification

Int. Cl.: **H01L21/02** (20060101); **C23C16/30** (20060101); **C23C16/32** (20060101); **C23C16/34** (20060101); **C23C16/36** (20060101); **C23C16/46** (20060101); **C23C16/52** (20060101)

U.S. Cl.:

CPC **H01L21/022** (20130101); **C23C16/308** (20130101); **C23C16/325** (20130101); **C23C16/345** (20130101); **C23C16/36** (20130101); **C23C16/46** (20130101); **C23C16/52** (20130101); **H01L21/0214** (20130101); **H01L21/02167** (20130101); **H01L21/0217** (20130101); **H01L21/0228** (20130101); **H01L21/02301** (20130101); **H01L21/02323** (20130101); **H01L21/02326** (20130101); **H01L21/02211** (20130101)

Field of Classification Search

CPC: H01L (21/022); H01L (21/0214); H01L (21/02167); H01L (21/0217); H01L (21/0228); H01L (21/02301); H01L (21/02323); H01L (21/02326); H01L (21/02211); H01L (21/67103); H01L (21/02126); H01L (21/02312); C23C (16/308); C23C (16/325); C23C (16/345); C23C (16/36); C23C (16/46); C23C (16/52); C23C (16/0218); C23C (16/401); C23C (16/45531)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
6271084	12/2000	Tu	257/E21.59	H01L 28/60
9548266	12/2016	Ajuria	N/A	H01L 24/02
9659998	12/2016	Lung	N/A	H10N 70/021
9899372	12/2017	Bi	N/A	H01L 28/82
9953830	12/2017	Ushida	N/A	C23C 16/45534
10395984	12/2018	Backes	N/A	H01L 23/528
10505111	12/2018	Ok	N/A	H01L 21/7682
10510951	12/2018	Yu	N/A	H10N 70/801
2007/0215852	12/2006	Lung	257/4	H10N 70/8413
2007/0232015	12/2006	Liu	257/E21.589	H10N 70/011
2008/0061282	12/2007	Sato	438/102	H10N 70/011
2008/0116437	12/2007	Oh	257/E47.001	H10N 70/8828
2008/0197335	12/2007	Yu	438/102	H10N 70/8265
2008/0280390	12/2007	Kim	438/95	H10B 63/30
2008/0303014	12/2007	Goux	438/102	H10N 70/043
2011/0155993	12/2010	Chen	438/102	H10N 70/8828
2011/0256733	12/2010	Hirose et al.	N/A	N/A
2012/0119177	12/2011	Erbetta	257/E21.52	H10N 70/8828
2012/0305872	12/2011	Yoon	257/532	H10N 70/882
2013/0149873	12/2012	Hirose et al.	N/A	N/A

2014/0051260	12/2013	Sasajima et al.	N/A	N/A
2014/0080314	12/2013	Sasajima et al.	N/A	N/A
2014/0138604	12/2013	Liu	257/4	H10N 70/231
2017/0062714	12/2016	Kau	N/A	H10N 70/8616
2018/0033607	12/2017	Nakatani	N/A	H01L 21/02167
2018/0342390	12/2017	Xiao	N/A	C23C 16/56
2019/0019673	12/2018	Ogawa	N/A	H01L 21/02208
2019/0088474	12/2018	MacDonald	N/A	C07F 7/10
2019/0189422	12/2018	Nakamura	N/A	C23C 16/45527
2019/0189688	12/2018	Lille	N/A	H10N 70/826
2019/0206679	12/2018	Maeda	N/A	H01L 21/02513
2020/0010954	12/2019	Bhuyan	N/A	C23C 16/401
2020/0152870	12/2019	Lin	N/A	H10N 70/8828
2020/0194670	12/2019	Allegra	N/A	H10N 70/841
2020/0219933	12/2019	Cheng	N/A	H10N 70/841
2021/0098532	12/2020	Wu	N/A	H10N 70/826
2022/0044929	12/2021	Xiao	N/A	C23C 16/401

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2011-238894	12/2010	JP	N/A
2013-140944	12/2012	JP	N/A
2014-038923	12/2013	JP	N/A
2014-060302	12/2013	JP	N/A

OTHER PUBLICATIONS

International Search Report, PCT/JP2019/008550, May 7, 2019, 5 pgs. cited by applicant

Primary Examiner: Henry; Caleb E

Attorney, Agent or Firm: Volpe Koenig

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a continuation of U.S. patent application Ser. No. 17/465,269, filed Sep. 2, 2021, which is a Bypass Continuation Application of PCT International Application No. PCT/JP2019/008550, filed Mar. 5, 2019, the entire content of which is incorporated herein by reference.

TECHNICAL FIELD

(1) The present disclosure relates to a method of manufacturing a semiconductor device, a method of processing a substrate, a substrate processing apparatus, and a recording medium.

BACKGROUND

(2) As a process of manufacturing a semiconductor device, a process of forming a low dielectric constant film on a heated substrate by supplying a process gas including an oxidizing gas to the substrate may be performed.

SUMMARY

(3) The present disclosure provides some embodiments of a technique capable of suppressing an oxidation of a film formed on a substrate when a base of the film is a metal-element-containing film, while the film is a low dielectric constant film.

(4) According to one or more embodiments of the present disclosure, there is provided a technique that includes: (a) loading a substrate where a conductive metal-element-containing film is exposed on a surface of the substrate into a process chamber under a first temperature; (b) supplying a reducing gas to the substrate while raising a temperature of the substrate to a second temperature higher than the first temperature in the process chamber; (c) forming a first film, which contains silicon and at least one selected from the group of nitrogen and carbon and does not contain oxygen, on the metal-element-containing film, by supplying a first process gas, which does not include an oxidizing gas, to the substrate under the second temperature in the process chamber; and (d) forming a second film, which contains silicon, oxygen, carbon, and nitrogen, on the first film such that the second film is thicker than the first film, by supplying a second process gas, which includes an oxidizing gas, to the substrate under a third temperature higher than the first temperature in the process chamber.

Description

BRIEF DESCRIPTION OF DRAWINGS

- (1) FIG. 1 is a schematic configuration view of a vertical process furnace of a substrate processing apparatus suitably used in one or more embodiments of the present disclosure, in which a portion of the process furnace is shown in a vertical cross section.
- (2) FIG. 2 is a schematic configuration view of the vertical process furnace of the substrate processing apparatus suitably used in the embodiments of the present disclosure, in which a portion of the process furnace is shown in a cross section taken along line A-A in FIG. 1.
- (3) FIG. 3 is a schematic configuration diagram of a controller of the substrate processing apparatus suitably used in the embodiments of the present disclosure, in which a control system of the controller is shown in a block diagram.
- (4) FIG. 4 is a diagram showing a substrate-processing sequence according to one or more embodiments of the present disclosure.
- (5) FIG. 5 is a diagram showing a gas-supplying sequence in first film formation according to one or more embodiments of the present disclosure.
- (6) FIG. 6 is a diagram showing a gas-supplying sequence in second film formation according to one or more embodiments of the present disclosure.
- (7) FIG. 7A is an enlarged cross-sectional view of the surface of a target wafer having a W film exposed on the surface of the wafer.
- (8) FIG. 7B is an enlarged cross-sectional view on the surface of the wafer after a ramp-up+H.sub.2 pre-flow is performed to remove a native oxide layer from the surface of the W film.
- (9) FIG. 7C is an enlarged cross-sectional view on the surface of the wafer after first film formation is performed to form a SiN film on the W film.
- (10) FIG. 7D is an enlarged cross-sectional view on the surface of the wafer after second film formation is performed to form a SiOCN film on the SiN film and the SiN film formed in the first film formation is modified into a SiON film.
- (11) FIG. 8 is a diagram showing the evaluation results regarding an oxidation-suppressing effect of the W film by performing the first film formation before the second film formation.

DETAILED DESCRIPTION

- (12) <One or More Embodiments of the Present Disclosure>
- (13) One or more embodiments of the present disclosure will be now described mainly with reference to FIGS. 1 to 7D.
- (14) (1) Configuration of Substrate Processing Apparatus
- (15) As shown in FIG. 1, a process furnace 202 includes a heater 207 as a heating mechanism (a temperature adjustment part). The heater 207 has a cylindrical shape and is supported by a support

plate so as to be vertically installed. The heater **207** also functions as an activation mechanism (an excitation part) configured to thermally activate (excite) a gas.

(16) A reaction tube **203** is disposed inside the heater **207** to be concentric with the heater **207**. The reaction tube **203** is made of, for example, a heat resistant material such as quartz (SiO₂) or silicon carbide (SiC), and has a cylindrical shape with its upper end closed and its lower end opened. A manifold **209** is disposed to be concentric with the reaction tube **203** under the reaction tube **203**. The manifold **209** is made of, for example, a metal material such as stainless steel (SUS), and has a cylindrical shape with both of its upper and lower ends opened. The upper end portion of the manifold **209** engages with the lower end portion of the reaction tube **203** so as to support the reaction tube **203**. An O-ring **220a** serving as a seal member is installed between the manifold **209** and the reaction tube **203**. Similar to the heater **207**, the reaction tube **203** is vertically installed. A process container (reaction container) mainly includes the reaction tube **203** and the manifold **209**. A process chamber **201** is formed in a hollow cylindrical portion of the process container. The process chamber **201** is configured to accommodate wafers **200** as substrates. Process to the wafers **200** is performed in the process chamber **201**.

(17) Nozzles **249a** and **249b** serving as first and second supply parts, respectively, are installed in the process chamber **201** so as to penetrate through a sidewall of the manifold **209**. The nozzles **249a** and **249b** are also referred to as first and second nozzles, respectively. The nozzles **249a** and **249b** are made of a non-metal material which is a heat resistant material such as quartz or SiC. The nozzles **249a** and **249b** are configured as common nozzles to be used for supplying a plurality of types of gases, respectively.

(18) Gas supply pipes **232a** and **232b** serving as first and second pipes, respectively, are connected to the nozzles **249a** and **249b**, respectively. The gas supply pipes **232a** and **232b** are configured as common pipes to be used for supplying a plurality of types of gases, respectively. Mass flow controllers (MFCs) **241a** and **241b**, which are flow rate controllers (flow rate control parts), and valves **243a** and **243b**, which are opening/closing valves, are installed in the gas supply pipes **232a** and **232b**, respectively, sequentially from the upstream side of a gas flow. Gas supply pipes **232e** and **232g** are connected to the gas supply pipe **232a** at the downstream side of the valves **243a**. MFCs **241e** and **241g** and valves **243e** and **243g** are installed in the gas supply pipes **232e** and **232g**, respectively, sequentially from the upstream side of a gas flow. Gas supply pipes **232c**, **232d**, **232f**, and **232h** are connected to the gas supply pipe **232b** at the downstream side of the valves **243b**. MFCs **241c**, **241d**, **241f**, and **241h** and valves **243c**, **243d**, **243f**, and **243h** are installed in the gas supply pipes **232c**, **232d**, **232f**, and **232h**, respectively, sequentially from the upstream side of a gas flow. The gas supply pipes **232a** to **232h** are made of, for example, a metal material such as SUS.

(19) As shown in FIG. 2, each of the nozzles **249a** and **249b** is disposed in an annular space in a plane view between an inner wall of the reaction tube **203** and the wafers **200** so as to extend upward from a lower portion of the inner wall of the reaction tube **203** to an upper portion thereof, that is, along an arrangement direction of the wafers **200**. Specifically, each of the nozzles **249a** and **249b** is installed in a region horizontally surrounding a wafer arrangement region in which the wafers **200** are arranged at a lateral side of the wafer arrangement region, along the wafer arrangement region. Gas supply holes **250a** and **250b** for supplying a gas are installed on the side surfaces of the nozzles **249a** and **249b**, respectively. Each of the gas supply holes **250a** and **250b** is opened toward the centers of the wafer **200**s in a plane view, which enables a gas to be supplied toward the wafers **200**. A plurality of gas supply holes **250a** and **250b** are installed from the lower portion of the reaction tube **203** to the upper portion thereof.

(20) A precursor gas, for example, a halosilane-based gas containing silicon (Si), which is a main element (predetermined element) constituting a film, and a halogen element is supplied from the gas supply pipe **232a** into the process chamber **201** via the MFC **241a**, the valve **243a**, and the nozzle **249a**. The precursor gas refers to a gaseous precursor, for example, a gas obtained by

vaporizing a precursor which remains in a liquid state at room temperature and atmospheric pressure, or a precursor which remains in a gas state at room temperature and atmospheric pressure. (21) Halosilane is a silane including a halogeno group (halogen group). The halogeno group includes a chloro group, a fluoro group, a bromo group, an iodine group, and the like. That is, the halogeno group contains chlorine (Cl), fluorine (F), bromine (Br), iodine (I), and the like. An example of the halosilane-based gas may include a precursor gas containing Si and Cl, that is, a chlorosilane-based gas. An example of the chlorosilane-based gas may include a hexachlorodisilane (Si.sub.2Cl.sub.6, abbreviation: HCDS) gas. The HCDS gas acts as a Si source.

(22) A reaction gas, for example, a nitrogen (N)- and hydrogen (H)-containing gas, is supplied from the gas supply pipe **232b** into the process chamber **201** via the MFC **241b**, the valve **243b**, and the nozzle **249b**. An example of the N- and H-containing gas may include an ammonia (NH.sub.3) gas which is a hydronitrogen-based gas. The NH.sub.3 gas acts as a nitriding gas, that is, a N source.

(23) A reaction gas, for example, a carbon (C)-containing gas, is supplied from the gas supply pipe **232c** into the process chamber **201** via the MFC **241c**, the valve **243c**, the gas supply pipe **232b**, and the nozzle **249b**. An example of the C-containing gas may include a propylene (C.sub.3H.sub.6) gas which is a hydrocarbon-based gas. The C.sub.3H.sub.6 gas acts as a C source.

(24) A reaction gas, for example, an oxygen (O)-containing gas, is supplied from the gas supply pipe **232d** into the process chamber **201** via the MFC **241d**, the valve **243d**, the gas supply pipe **232b**, and the nozzle **249b**. An example of the O-containing gas may include an oxygen (O₂) gas. The O.sub.2 gas acts as an oxidizing gas, that is, an O source.

(25) A reducing gas, for example, a hydrogen (H.sub.2) gas, which is a H-containing gas, is supplied from the gas supply pipes **232e** and **232f** into the process chamber **201** via the MFCs **241e** and **241f**, the valves **243e** and **243f**, the gas supply pipes **232a** and **232b**, and the nozzles **249a** and **249b**, respectively.

(26) An inert gas, for example, a nitrogen (N.sub.2) gas, is supplied from the gas supply pipes **232g** and **232h** into the process chamber **201** via the MFCs **241g** and **241h**, the valves **243g** and **243h**, the gas supply pipes **232a** and **232b**, and the nozzles **249a** and **249b**, respectively. The N.sub.2 gas acts as a purge gas, a carrier gas, a dilution gas, or the like.

(27) A precursor gas supply system (Si source supply system) mainly includes the gas supply pipe **232a**, the MFC **241a**, and the valve **243a**. A reaction gas supply system (N source supply system, C source supply system, and O source supply system) mainly includes the gas supply pipes **232b** to **232d**, the MFCs **241b** to **241d**, and the valves **243b** to **243d**. A reducing gas supply system mainly includes the gas supply pipes **232e** and **232f**, the MFCs **241e** and **241f**, and the valves **243e** and **243f**. An inert gas supply system mainly includes the gas supply pipes **232g** and **232h**, the MFCs **241g** and **241h**, and the valves **243g** and **243h**.

(28) The precursor gas and the reaction gas to be used in first film formation, which will be described later, are also collectively referred to as a first process gas. Further, the precursor gas supply system and the reaction gas supply system to be used in the first film formation are also collectively referred to as a first process gas supply system. Further, the precursor gas and the reaction gas to be used in second film formation, which will be described later, are also collectively referred to as a second process gas. Further, the precursor gas supply system and the reaction gas supply system to be used in the second film formation are also collectively referred to as a second process gas supply system.

(29) One or all of the above-described various supply systems may be configured as an integrated-type supply system **248** in which the valves **243a** to **243h**, the MFCs **241a** to **241h**, and so on are integrated. The integrated-type supply system **248** is connected to each of the gas supply pipes **232a** to **232h**. In addition, the integrated-type supply system **248** is configured such that operations of supplying various gases into the gas supply pipes **232a** to **232h** (that is, the opening/closing operation of the valves **243a** to **243h**, the flow rate adjustment operation by the MFCs **241a** to **241h**, and the like) are controlled by a controller **121** which will be described later. The integrated-

type supply system **248** is configured as an integral type or detachable type integrated unit, and may be attached to and detached from the gas supply pipes **232a** to **232h** and the like on an integrated unit basis, so that the maintenance, replacement, extension, etc. of the integrated-type supply system **248** can be performed on an integrated unit basis.

(30) An exhaust port **231a** for exhausting an internal atmosphere of the process chamber **201** is installed below the sidewall of the reaction tube **203**. The exhaust port **231a** may be installed from a lower portion of the sidewall of the reaction tube **203** to an upper portion thereof, that is, along the wafer arrangement region. An exhaust pipe **231** is connected to the exhaust port **231a**. A vacuum exhaust device, for example, a vacuum pump **246**, is connected to the exhaust pipe **231** via a pressure sensor **245**, which is a pressure detector (pressure detecting part) for detecting the internal pressure of the process chamber **201**, and an auto pressure controller (APC) valve **244**, which is a pressure regulator (pressure adjustment part). The APC valve **244** is configured to perform or stop a vacuum exhausting operation in the process chamber **201** by opening/closing the valve while the vacuum pump **246** is actuated, and is also configured to adjust the internal pressure of the process chamber **201** by adjusting an opening degree of the valve based on pressure information detected by the pressure sensor **245** while the vacuum pump **246** is actuated. An exhaust system mainly includes the exhaust pipe **231**, the APC valve **244**, and the pressure sensor **245**. The exhaust system may include the vacuum pump **246**.

(31) A seal cap **219**, which serves as a furnace opening cover configured to hermetically seal a lower end opening of the manifold **209**, is installed under the manifold **209**. The seal cap **219** is made of, for example, a metal material such as SUS, and is formed in a disc shape. An O-ring **220b**, which is a seal member making contact with the lower end portion of the manifold **209**, is installed on an upper surface of the seal cap **219**. A rotation mechanism **267** configured to rotate a boat **217**, which will be described later, is installed under the seal cap **219**. A rotary shaft **255** of the rotation mechanism **267** is connected to the boat **217** via the seal cap **219**. The rotation mechanism **267** is configured to rotate the wafers **200** by rotating the boat **217**. The seal cap **219** is configured to be vertically moved up and down by a boat elevator **115** which is an elevating mechanism installed outside the reaction tube **203**. The boat elevator **115** is configured as a transfer system (transfer mechanism) which loads/unloads (transfers) the wafers **200** into/out of the process chamber **201** by moving the seal cap **219** up and down. A shutter **219s**, which serves as a furnace opening cover configured to hermetically seal a lower end opening of the manifold **209** in a state where the seal cap **219** is lowered and the boat **217** is unloaded from an interior of the process chamber **201**, is installed under the manifold **209**. The shutter **219s** is made of, for example, a metal material such as SUS, and is formed in a disc shape. An O-ring **220c**, which is a seal member making contact with the lower end portion of the manifold **209**, is installed on an upper surface of the shutter **219s**. The opening/closing operation (such as elevation operation, rotation operation, or the like) of the shutter **219s** is controlled by a shutter-opening/closing mechanism **115s**.

(32) The boat **217** serving as a substrate support is configured to support a plurality of wafers **200**, for example, 25 to 200 wafers, in such a state that the wafers **200** are arranged in a horizontal posture and in multiple stages along a vertical direction with the centers of the wafers **200** aligned with one another. As such, the boat **217** is configured to arrange the wafers **200** to be spaced apart from each other. The boat **217** is made of a heat resistant material such as quartz or SiC. Heat-insulating plates **218** made of a heat resistant material such as quartz or SiC are supported below the boat **217** in multiple stages.

(33) A temperature sensor **263** serving as a temperature detector is installed in the reaction tube **203**. Based on temperature information detected by the temperature sensor **263**, a degree of supplying electric power to the heater **207** is adjusted such that the interior of the process chamber **201** has a desired temperature distribution. The temperature sensor **263** is installed along the inner wall of the reaction tube **203**.

(34) As shown in FIG. 3, a controller **121**, which is a control part (control means), is configured as

a computer including a central processing unit (CPU) **121a**, a random access memory (RAM) **121b**, a memory **121c**, and an I/O port **121d**. The RAM **121b**, the memory **121c**, and the I/O port **121d** are configured to be capable of exchanging data with the CPU **121a** via an internal bus **121e**. An input/output device **122** formed of, e.g., a touch panel or the like, is connected to the controller **121**.

(35) The memory **121c** is configured by, for example, a flash memory, a hard disk drive (HDD), or the like. A control program for controlling operations of a substrate processing apparatus, a process recipe in which sequences and conditions of substrate processing to be described later are written, etc. are readably stored in the memory **121c**. The process recipe functions as a program for causing the controller **121** to execute each sequence in the substrate processing, which will be described later, to obtain an expected result. Hereinafter, the process recipe and the control program may be generally and simply referred to as a “program.” Furthermore, the process recipe may be simply referred to as a “recipe.” When the term “program” is used herein, it may indicate a case of including the recipe only, a case of including the control program only, or a case of including both the recipe and the control program. The RAM **121b** is configured as a memory area (work area) in which a program or data read by the CPU **121a** is temporarily stored.

(36) The I/O port **121d** is connected to the MFCs **241a** to **241h**, the valves **243a** to **243h**, the pressure sensor **245**, the APC valve **244**, the vacuum pump **246**, the temperature sensor **263**, the heater **207**, the rotation mechanism **267**, the boat elevator **115**, the shutter-opening/closing mechanism **115s**, and so on.

(37) The CPU **121a** is configured to read and execute the control program from the memory **121c** and is also configured to read the recipe from the memory **121c** according to an input of an operation command from the input/output device **122**. The CPU **121a** is configured to control the flow-rate-adjusting operation of various kinds of gases by the MFCs **241a** to **241h**, the opening/closing operation of the valves **243a** to **243h**, the opening/closing operation of the APC valve **244**, the pressure adjusting operation performed by the APC valve **244** based on the pressure sensor **245**, the actuating and stopping operation of the vacuum pump **246**, the temperature adjusting operation performed by the heater **207** based on the temperature sensor **263**, the operations of rotating the boat **217** and adjusting the rotation speed of the boat **217** with the rotation mechanism **267**, the operation of moving the boat **217** up and down by the boat elevator **115**, the opening/closing operation of the shutter **219s** by the shutter-opening/closing mechanism **115s**, and so on, according to contents of the read recipe.

(38) The controller **121** may be configured by installing, on the computer, the aforementioned program stored in an external memory **123**. Examples of the external memory **123** may include a magnetic disk such as a HDD, an optical disc such as a CD, a magneto-optical disc such as a MO, a semiconductor memory such as a USB memory, and the like. The memory **121c** or the external memory **123** is configured as a non-transitory computer-readable recording medium. Hereinafter, the memory **121c** and the external memory **123** may be generally and simply referred to as a “recording medium.” When the term “recording medium” is used herein, it may indicate a case of including the memory **121c** only, a case of including the external memory **123** only, or a case of including both the memory **121c** and the external memory **123**. Furthermore, the program may be provided to the computer using communication means such as the Internet or a dedicated line, instead of using the external memory **123**.

(39) (2) Substrate-Processing Process

(40) As a process of manufacturing a semiconductor device using the above-described substrate processing apparatus, a substrate-processing sequence example of removing a native oxide film formed on the surface of a conductive metal-element-containing film (hereinafter also simply referred to as a metal-containing film) exposed on a wafer **200** as a substrate and then forming a low dielectric constant film on the metal-containing film while suppressing oxidation of the metal-containing film will be described mainly with reference to FIGS. **4** to **7D**. In the following

descriptions, the operations of the respective parts constituting the substrate processing apparatus are controlled by the controller **121**.

(41) The substrate-processing sequence shown in FIG. **4** includes: a step of loading a wafer **200** having a tungsten (W) film as a conductive metal-element-containing film exposed on the surface of the wafer **200** into a process chamber **201** under a first temperature (wafer charging and boat loading); a step of supplying a H.sub.2 gas as a reducing gas to the wafer **200** while raising the temperature of the wafer **200** to a second temperature higher than the first temperature in the process chamber **201** (ramp-up+H.sub.2 pre-flow); a step of forming a silicon nitride film (SiN film) as a first film containing Si and at least one selected from the group of N and C and not containing O on the W film by supplying a HCDS gas and an NH.sub.3 gas as a first process gas including no oxidizing gas to the wafer **200** in the process chamber **201** under the second temperature (first film formation); and a step of forming a silicon oxycarbonitride film (SiOCN film) as a second film containing Si, O, C, and N, which is thicker than the SiN film, on the SiN film by supplying a HCDS gas, an O.sub.2 gas, a C.sub.3H.sub.6 gas, and an NH.sub.3 gas as a second process gas including an oxidizing gas to the wafer **200** in the process chamber **201** under a third temperature higher than the first temperature (second film formation).

(42) In the first film formation described above, a cycle which includes supplying the HCDS gas and the NH.sub.3 gas to the wafer **200** is performed a predetermined number of times. In a gas-supplying sequence shown in FIG. **5**, in the first film formation, a sequence example of performing a cycle m times (where m is an integer of 1 or more and 3 or less), the cycle including intermittently and non-simultaneously supplying the HCDS gas and the NH.sub.3 gas to the wafer **200**, is shown.

(43) Further, in the second film formation described above, a cycle which includes supplying the HCDS gas, the O.sub.2 gas, the C.sub.3H.sub.6 gas, and the NH.sub.3 gas to the wafer **200** is performed a predetermined number of times. In a gas-supplying sequence shown in FIG. **6**, in the second film formation, a sequence example of performing a cycle n times (where n is an integer of 1 or more), the cycle including intermittently and non-simultaneously supplying the HCDS gas, the O.sub.2 gas, the C.sub.3H.sub.6 gas, and the NH.sub.3 gas to the wafer **200**, is shown.

(44) In the present disclosure, the gas-supplying sequence of the first film formation shown in FIG. **5** and the gas-supplying sequence of the second film formation shown in FIG. **6** may be denoted as follows for the sake of convenience. The same notation will be used in the following description of other embodiments.

(HCDS.fwdarw.NH.sub.3) $\times$ m.Math.SiN

(HCDS.fwdarw.C.sub.3H.sub.6.fwdarw.O.sub.2.fwdarw.NH.sub.3) $\times$ n.Math.SiOCN

(45) When the term “wafer” is used in the present disclosure, it may refer to “a wafer itself” or “a wafer and a laminated body of certain layers or films formed on a surface of the wafer.” When the phrase “a surface of a wafer” is used in the present disclosure, it may refer to “a surface of a wafer itself” or “a surface of a certain layer formed on a wafer.” When the expression “a certain layer is formed on a wafer” is used in the present disclosure, it may mean that “a certain layer is formed directly on a surface of a wafer itself” or that “a certain layer is formed on a layer formed on a wafer.” When the term “substrate” is used in the present disclosure, it may be synonymous with the term “wafer.”

(46) (Wafer Charging and Boat Loading)

(47) When the boat **217** is charged with a plurality of wafers **200** (wafer charging), the shutter **219s** is moved by the shutter-opening/closing mechanism **115s** and the lower end opening of the manifold **209** is opened (shutter open). Thereafter, as shown in FIG. **1**, the boat **217** supporting the wafers **200** is lifted up by the boat elevator **115** to be loaded into the process chamber **201** (boat loading). In this state, the seal cap **219** seals the lower end of the manifold **209** via the O-ring **220b**.

(48) As a wafer **200**, for example, a Si substrate composed of single crystal Si or a substrate having a single crystal Si film formed on the surface of the substrate can be used. As shown in FIG. **7A**, a

W film, which is a conductive metal-element-containing film, is installed in at least a portion of the surface of the wafer **200**, and at least a portion of the W film is exposed. A native oxide layer may be formed on the exposed surface of the W film. In the W film, the ratio (%) of the thickness of a W layer, which is a portion where the native oxide layer is not formed (not oxidized), and the thickness of a layer having the composition of WO_{sub}.x (hereinafter also simply referred to as a WO layer), which is a portion where the native oxide layer is formed (oxidized), is, for example, about 70:30.

(49) When the boat is loaded, in order to suppress the oxidation of the W film, that is, in order to suppress formation of a further WO layer on the surface of the W film, increase in the thickness of the already-formed WO layer, etc., it is preferable that the internal temperature of the process chamber **201** is set to a predetermined first temperature, that is, a predetermined temperature within a range of room temperature (25 degrees C.) or higher and 200 degrees C. or lower, specifically room temperature or higher and 150 degrees C. or lower. When the internal temperature of the process chamber **201** exceeds 200 degrees C., oxidation of the W film may proceed due to the influence of the moisture infiltrated into the process chamber **201** when the boat is loaded, the moisture remaining in the process chamber **201** before the boat loading, etc. By setting the internal temperature of the process chamber **201** to 200 degrees C. or lower, it is less susceptible to the influence of the moisture infiltrated into the process chamber **201**, the moisture remaining in the process chamber **201**, etc., which makes it possible to avoid the oxidation of the W film. By setting the internal temperature of the process chamber **201** to 150 degrees C. or lower, it is possible to reliably avoid the oxidation of the W film when the boat is loaded. When the internal temperature of the process chamber **201** is lower than the room temperature, a cooling device for cooling the interior of the process chamber **201** may be required, and the subsequent temperature-rising time becomes long. As a result, the apparatus costs may increase and the productivity may decrease. By setting the internal temperature of the process chamber **201** to the room temperature or higher, a cooling device for cooling the interior of the process chamber **201** may not be required, and the subsequent temperature-rising time can be shortened. As a result, it is possible to reduce the apparatus costs and improve the productivity.

(50) Further, when the boat is loaded, the valves **243g** and **243h** are opened to allow a N_{sub}.2 gas to be supplied into the process chamber **201** via the nozzles **249a** and **249b** to purge the interior of the process chamber **201** with the N_{sub}.2 gas. As a result, it is possible to prevent the infiltration of water and the like into the process chamber **201**, promote the discharge of the residual water and the like from the interior of the process chamber **201**, etc. The supply flow rate of the N_{sub}.2 gas (for each gas supply pipe) is a flow rate within a range of, for example, 0.5 to 20 slm.

(51) As an inert gas, in addition to the N_{sub}.2 gas, a rare gas such as an Ar gas, a He gas, a Ne gas, a Xe gas, or the like can be used. The same applies to each step to be described later.

(52) (Ramp-Up+H_{sub}.2 Pre-Flow)

(53) After the boat load is completed, the interior of the process chamber **201** is vacuum-exhausted (depressurization-exhausted) by the vacuum pump **246** to reach a desired pressure (pressure adjustment). Further, the wafer **200** in the process chamber **201** is heated to rise in temperature by the heater **207** to reach a desired second temperature higher than the first temperature (ramp-up). Further, the rotation mechanism **267** starts to rotate the wafer **200** (rotation). The exhaust of the interior of the process chamber **201** and the heating and rotation of the wafer **200** are continuously performed at least until the process to the wafer **200** is completed.

(54) Then, in parallel with the ramp-up (temperature rise) of the wafer **200**, H_{sub}.2 pre-flow is performed. That is, the valves **243e** and **243f** are opened to allow a H_{sub}.2 gas to flow into the gas supply pipes **232e** and **232f**. The flow rate of the H_{sub}.2 gas is adjusted by the MFC **241e** and **241f**, and the H_{sub}.2 gas is supplied into the process chamber **201** via the nozzles **249a** and **249b** and is exhausted through the exhaust port **231a**. In this operation, the H_{sub}.2 gas is supplied to the wafer **200** (H_{sub}.2 pre-flow). At this time, the valves **243g** and **243h** may be opened to allow a

N.sub.2 gas to be supplied into the process chamber **201** via the nozzles **249a** and **249b**.

(55) The process conditions of this step are exemplified as follows. H.sub.2 gas supply flow rate (for each gas supply pipe): 1 to 10 slm N.sub.2 gas supply flow rate (for each gas supply pipe): 1 to 10 slm Each gas supply time: 1 to 120 minutes, specifically 1 to 60 minutes Temperature-rising start temperature (first temperature): room temperature to 200 degrees C., specifically room temperature to 150 degrees C. Temperature-rising target temperature (second temperature): 500 to 800 degrees C., specifically 600 to 700 degrees C. Temperature-rising rate: 1 to 30 degrees C./min, specifically 1 to 20 degrees C./min Processing pressure: 20 to 10,000 Pa, specifically 1,000 to 5,000 Pa The temperature-rising target temperature is also the processing temperature in the first film formation to be described later.

(56) By supplying the H.sub.2 gas to the wafer **200** while raising the temperature of the wafer **200** under the aforementioned conditions, that is, by raising the temperature of the wafer **200** under the H.sub.2 gas atmosphere, it is possible to reduce a portion of the W film, which is exposed to the surface of the wafer **200** to remove the WO layer formed on the surface of the W film, as shown in FIG. 7B. The component contained in the WO layer constitutes a gaseous substance containing at least O in the process of a reaction that occurs when the WO layer is removed, and is discharged from the process chamber **201**. Further, in this step, by raising the temperature of the wafer **200** under the H.sub.2 gas atmosphere, it is possible to prevent the oxidation of the surface of the W film after the WO layer is removed.

(57) If the second temperature is lower than 500 degrees C., the effect of removing the WO layer by the reduction reaction described above and the effect of preventing the oxidation of the surface of the W film after removing the WO layer may be insufficient. By setting the second temperature to a temperature of 500 degrees C. or higher, these effects can be sufficiently obtained. By setting the second temperature to a temperature of 600 degrees C. or higher, these effects can be surely obtained.

(58) If the second temperature exceeds 800 degrees C., an excessive vapor phase reaction may occur in the process chamber **201** in the first film formation to be described later, which may deteriorate the film thickness uniformity of the film formed on the wafer **200**, thereby deteriorating the quality of the film. By setting the second temperature to 800 degrees C. or lower, this problem can be solved. By setting the second temperature to 700 degrees C. or lower, this problem can be surely solved.

(59) As a reducing gas, a deuterium (D.sub.2) gas can be used in addition to the H.sub.2 gas.

(60) After the removal of the WO layer from the surface of the W film is completed, the valves **243e** and **243f** are closed to stop the supply of the H.sub.2 gas into the process chamber **201**. Then, the interior of the process chamber **201** is vacuum-exhausted to remove a gas and the like remaining in the process chamber **201** from the interior of the process chamber **201** (purge). At this time, the valves **243g** and **243h** are opened to allow a N.sub.2 gas to be supplied into the process chamber **201**. The N.sub.2 gas acts as a purge gas. Even after the removal of the WO layer from the surface of the W film is completed, the supply of the H.sub.2 gas into the process chamber **201** may be continued (maintained) for a predetermined period until the first film formation is started. For example, even after the temperature rise of the wafer **200** to the second temperature is completed, the supply of the H.sub.2 gas into the process chamber **201** may be continued for a predetermined period until the first film formation is started. In this case, the effect of preventing the oxidation of the surface of the W film after the WO layer is removed can be continued for a predetermined period until the first film formation is started.

(61) (First Film Formation)

(62) After that, the next steps C1 and C2 are sequentially executed.

(63) [Step C1]

(64) In this step, a HCDS gas is supplied to the wafer **200** in the process chamber **201** (HCDS gas supply). Specifically, the valve **243a** is opened to allow the HCDS gas to flow into the gas supply

pipe **232a**. The flow rate of the HCDS gas is adjusted by the MFC **241a**, and the HCDS gas is supplied into the process chamber **201** via the nozzle **249a** and is exhausted through the exhaust port **231a**. In this operation, the HCDS gas is supplied to the wafer **200**. At this time, the valves **243g** and **243h** may be opened to allow a N.sub.2 gas to be supplied into the process chamber **201** via the nozzles **249a** and **249b**.

(65) The process conditions of this step are exemplified as follows. HCDS gas supply flow rate: 0.01 to 2 slm, specifically 0.1 to 1 slm N.sub.2 gas supply flow rate (for each gas supply pipe): 0 to 10 slm Each gas supply time: 1 to 120 seconds, specifically 1 to 60 seconds Processing temperature (second temperature): 500 degrees C. to 800 degrees C., specifically 600 degrees C. to 700 degrees C. Processing pressure: 1 to 2,666 Pa, specifically 67 to 1,333 Pa

(66) By supplying the HCDS gas to the wafer **200** under the aforementioned conditions, a Si-containing layer containing Cl is formed on the outermost surface of the wafer **200**. The Si-containing layer containing Cl is formed by Si deposition or the like on the outermost surface of the wafer **200** by physical adsorption of HCDS, chemical adsorption of a substance (hereinafter, Si.sub.xCl.sub.y) obtained when a portion of HCDS is decomposed, thermal decomposition of HCDS, and the like. The Si-containing layer containing Cl may be an adsorption layer (physical adsorption layer or chemical adsorption layer) of HCDS or Si.sub.xCl.sub.y, or may be a Si deposition layer containing Cl. In the present disclosure, the Si-containing layer containing Cl is also simply referred to as a Si-containing layer.

(67) After the Si-containing layer is formed, the valve **243a** is closed to stop the supply of the HCDS gas into the process chamber **201**. Then, the interior of the process chamber **201** is vacuum-exhausted to remove a gas and the like remaining in the process chamber **201** from the interior of the process chamber **201**. At this time, the valves **243g** and **243h** are opened to allow a N.sub.2 gas to flow into the process chamber **201**. The N.sub.2 gas acts as a purge gas.

(68) As a precursor gas, in addition to the HCDS gas, it may be possible to use, e.g., a chlorosilane-based gas such as a monochlorosilane (SiH.sub.3Cl, abbreviation: MCS) gas, a dichlorosilane (SiH.sub.2Cl.sub.2, abbreviation: DCS) gas, a trichlorosilane (SiHCl.sub.3, abbreviation: TCS) gas, a tetrachlorosilane (SiCl.sub.4, abbreviation: STC) gas, or an octachlorotrisilane (Si.sub.3Cl.sub.8, abbreviation: OCTS) gas. The same applies to step D1 to be described later.

(69) [Step C2]

(70) After step C1 is completed, an NH.sub.3 gas is supplied to the wafer **200** in the process chamber **201**, that is, the Si-containing layer formed on the wafer **200** (NH.sub.3 gas supply). Specifically, the valve **243b** is opened to allow the NH.sub.3 gas to flow into the gas supply pipe **232b**. The flow rate of the NH.sub.3 gas is adjusted by the MFC **241b**, and the NH.sub.3 gas is supplied into the process chamber **201** via the nozzle **249b** and is exhausted through the exhaust port **231a**. In this operation, the NH.sub.3 gas is supplied to the wafer **200**. At this time, the valves **243g** and **243h** may be opened to allow a N.sub.2 gas to be supplied into the process chamber **201** via the nozzles **249a** and **249b**.

(71) The process conditions of this step are exemplified as follows. NH.sub.3 gas supply flow rate: 0.1 to 10 slm NH.sub.3 gas supply time: 1 to 120 seconds, specifically 1 to 60 seconds Processing pressure: 1 to 4,000 Pa, specifically 1 to 3,000 Pa Other process conditions are the same as the process conditions in step C1.

(72) By supplying the NH.sub.3 gas to the wafer **200** under the aforementioned conditions, at least a portion of the Si-containing layer formed on the wafer **200** is nitrided (modified). By modifying the Si-containing layer, a layer containing Si and N, that is, a silicon nitride layer (SiN layer), is formed on the wafer **200**. When forming the SiN layer, impurities such as Cl contained in the Si-containing layer constitute a gaseous substance containing at least Cl in the process of modifying the Si-containing layer with the NH.sub.3 gas and are discharged from the interior of the process chamber **201**. As a result, the SiN layer becomes a layer having fewer impurities such as Cl than the Si-containing layer formed in step C1.

(73) After the SiN layer is formed, the valve **243b** is closed to stop the supply of the NH₃ gas into the process chamber **201**. Then, a gas and the like remaining in the process chamber **201** are removed from the process chamber **201** according to the same processing procedure as in the purge in step C1 (purge).

(74) As a reaction gas (N- and H-containing gas), in addition to the NH₃ gas, it may be possible to use, e.g., a hydrogen nitride-based gas such as a diazene (N₂H₂) gas, a hydrazine (N₂H₄) gas, or a N₃H₈ gas. The same applies to step D4 to be described later.

(75) (Performing Predetermined Number of Times)

(76) By performing a cycle a predetermined number of times (m times, where m is an integer of 1 or more and 3 or less), the cycle including non-simultaneously, that is, without synchronization, performing the above-described steps 1 and 2, as shown in FIG. 7C, it is possible to form a SiN film having a predetermined composition and a predetermined film thickness on the wafer **200**, that is, the W film from which the WO layer is removed by the temperature rise of the wafer **200** under the H₂ gas atmosphere.

(77) The thickness of the SiN film is, for example, 0.16 nm or more and 1 nm or less, specifically 0.16 nm or more and 0.48 nm or less, and more specifically 0.16 nm or more and 0.32 nm or less.

(78) If the thickness of the SiN film is less than 0.16 nm, the oxidation-blocking effect to be described later becomes insufficient, so that a portion of the W film may be oxidized in the second film formation to be described later. By setting the thickness of the SiN film to 0.16 nm or more, the oxidation-blocking effect can be sufficiently obtained, which makes it possible to avoid the oxidation of the W film in the second film formation to be described later.

(79) If the thickness of the SiN film exceeds 1 nm, the total dielectric constant of a laminated film to be described later may increase. By setting the thickness of the SiN film to 1 nm or less, it is possible to suppress the increase in the total dielectric constant of the laminated film to be described later. By setting the thickness of the SiN film to 0.48 nm or less, this effect can be surely obtained, and by setting the thickness of the SiN film to 0.32 nm or less, this effect can be more surely obtained.

(80) The above-mentioned cycle may be repeated multiple times. That is, the thickness of the SiN layer formed when the above-mentioned cycle is performed once may be set to be smaller than a desired film thickness, and the above-mentioned cycle may be repeated multiple times until the film thickness of a SiN film formed by laminating SiN layers reaches the desired film thickness. By setting the number of times of performing the above-mentioned cycle to a predetermined number of times of 1 or more and 3 or less, it is possible to set the thickness of the SiN film within the above-mentioned range.

(81) (Second Film Formation)

(82) After that, the next steps D1 to D4 are sequentially executed.

(83) [Step D1]

(84) In this step, a HCDS gas is supplied to the wafer **200** in the process chamber **201** according to the same processing procedure as the processing procedure in the above-described step C1 (HCDS gas supply).

(85) The process conditions of this step are exemplified as follows. HCDS gas supply flow rate: 0.01 to 2 slm, specifically 0.1 to 1 slm N₂ gas supply flow rate (for each gas supply pipe): 0 to 10 slm Each gas supply time: 1 to 120 seconds, specifically 1 to 60 seconds Processing temperature (third temperature): 250 degrees C. to 800 degrees C., specifically 400 degrees C. to 700 degrees C. Processing pressure: 1 to 2,666 Pa, specifically 67 to 1,333 Pa

(86) The third temperature may be a temperature higher than the above-mentioned first temperature. Further, the third temperature may be the same as the above-mentioned second temperature.

(87) By supplying the HCDS gas to the wafer **200** under the aforementioned conditions, a Si-

containing layer is formed on the wafer **200**, that is, on the SiN film formed on the wafer **200**.

(88) After the Si-containing layer is formed, the supply of the HCDS gas into the process chamber **201** is stopped, and a gas and the like remaining in the process chamber **201** are removed from the process chamber **201** according to the same processing procedure as in the purge in step C1 (purge).

(89) [Step D2]

(90) After step D1 is completed, a C.sub.3H.sub.6 gas is supplied to the wafer **200** in the process chamber **201**, that is, the Si-containing layer formed on the SiN film on the wafer **200**

(C.sub.3H.sub.6 gas supply). Specifically, the valve **243c** is opened to allow the C.sub.3H.sub.6 gas to flow into the gas supply pipe **232c**. The flow rate of the C.sub.3H.sub.6 gas is adjusted by the MFC **241c**, and the C.sub.3H.sub.6 gas is supplied into the process chamber **201** via the gas supply pipe **232b** and the nozzle **249b** and is exhausted through the exhaust port **231a**. In this operation, the C.sub.3H.sub.6 gas is supplied to the wafer **200**. At this time, the valves **243g** and **243h** may be opened to allow a N.sub.2 gas to be supplied into the process chamber **201** via the nozzles **249a** and **249b**.

(91) The process conditions of this step are exemplified as follows. C.sub.3H.sub.6 gas supply flow rate: 0.1 to 10 slm C.sub.3H.sub.6 gas supply time: 1 to 120 seconds, specifically 1 to 60 seconds Processing pressure: 1 to 4,000 Pa, specifically 1 to 3,000 Pa Other process conditions are the same as the process conditions in step D1.

(92) By supplying the C.sub.3H.sub.6 gas to the wafer **200** under the aforementioned conditions, a C-containing layer is formed on the Si-containing layer. As a result, a layer containing Si and C formed by laminating the C-containing layer on the Si-containing layer is formed on the wafer **200**, that is, on the SiN film on the wafer **200**.

(93) After the layer containing Si and C is formed, the valve **243c** is closed to stop the supply of the C.sub.3H.sub.6 gas into the process chamber **201**. Then, a gas and the like remaining in the process chamber **201** are removed from the process chamber **201** according to the same processing procedure as in the purge in step C1 (purge).

(94) As a reaction gas (C-containing gas), in addition to the C.sub.3H.sub.6 gas, it may be possible to use, e.g., a hydrocarbon-based gas such as an acetylene (C.sub.2H.sub.2) gas or an ethylene (C.sub.2H.sub.4) gas.

(95) [Step D3]

(96) After step D2 is completed, an O.sub.2 gas is supplied to the wafer **200** in the process chamber **201**, that is, the layer containing Si and C formed on the SiN film on the wafer **200** (O.sub.2 gas supply). Specifically, the valve **243d** is opened to allow the O.sub.2 gas to flow into the gas supply pipe **232d**. The flow rate of the O.sub.2 gas is adjusted by the MFC **241d**, and the O.sub.2 is supplied into the process chamber **201** via the gas supply pipe **232b** and the nozzle **249b** and is exhausted through the exhaust port **231a**. In this operation, the O.sub.2 gas is supplied to the wafer **200**. At this time, the valves **243g** and **243h** may be opened to allow a N.sub.2 gas to be supplied into the process chamber **201** via the nozzles **249a** and **249b**.

(97) The process conditions of this step are exemplified as follows. O.sub.2 gas supply flow rate: 0.1 to 10 slm O.sub.2 gas supply time: 1 to 120 seconds, specifically 1 to 60 seconds Processing pressure: 1 to 4,000 Pa, specifically 1 to 3,000 Pa Other process conditions are the same as the process conditions in step D1.

(98) By supplying the O.sub.2 gas to the wafer **200** under the aforementioned conditions, at least a portion of the layer containing Si and C formed on the SiN film on the wafer **200** is oxidized (modified). By modifying the layer containing Si and C, a silicon oxycarbide layer (SiOC layer) is formed as a layer containing Si, O, and C on the wafer **200**, that is, on the SiN film on the wafer **200**. When the SiOC layer is formed, impurities such as Cl contained in the layer containing Si and C constitute a gaseous substance containing at least Cl in the process of modifying the layer containing Si and C with the O.sub.2 gas and are discharged from the interior of the process

chamber **201**. As a result, the SiOC layer becomes a layer having fewer impurities such as Cl than the Si-containing layer formed in step D1 and the layer containing Si and C formed in step D2. (99) After the SiOC layer is formed, the valve **243d** is closed to stop the supply of the O.sub.2 gas into the process chamber **201**. Then, a gas and the like remaining in the process chamber **201** are removed from the process chamber **201** according to the same processing procedure as in the purge in step C1 (purge).

(100) As a reaction gas (O-containing gas), in addition to the O.sub.2 gas, it may be possible to use, e.g., an ozone (O.sub.3) gas, water vapor (H.sub.2O gas), a nitric oxide (NO) gas, or a nitrous oxide (N.sub.2O) gas.

(101) [Step D4]

(102) After step D3 is completed, an NH.sub.3 gas is supplied to the wafer **200** in the process chamber **201** according to the same processing procedure as the processing procedure in the above-described step C2 (NH.sub.3 gas supply).

(103) The process conditions of this step are exemplified as follows. NH.sub.3 gas supply flow rate: 0.1 to 10 slm NH.sub.3 gas supply time: 1 to 120 seconds, specifically 1 to 60 seconds Processing pressure: 1 to 4,000 Pa, specifically 1 to 3,000 Pa Other process conditions are the same as the process conditions in step D1.

(104) By supplying the NH.sub.3 gas to the wafer **200** under the aforementioned conditions, at least a portion of the SiOC layer formed on the SiN film on the wafer **200** is nitrided (modified). By modifying the SiOC layer, a silicon oxycarbonitride layer (SiOCN layer) is formed as a layer containing Si, O, C, and N on the wafer **200**, that is, on the SiN film on the wafer **200**. When the SiOCN layer is formed, impurities such as Cl contained in the SiOC layer constitute a gaseous substance containing at least Cl in the process of modifying the SiOC layer with the NH.sub.3 gas and are discharged from the interior of the process chamber **201**. As a result, the SiOCN layer becomes a layer having fewer impurities such as Cl than the SiOC layer formed in step D3.

(105) After the SiOCN layer is formed, the supply of the NH.sub.3 gas into the process chamber **201** is stopped, and a gas and the like remaining in the process chamber **201** are removed from the interior of the process chamber **201** according to the same processing procedure as in the purge in step C1 (purge).

(106) (Performing Predetermined Number of Times)

(107) By performing a cycle a predetermined number of times (n times, where n is an integer of 1 or more), the cycle including non-simultaneously, that is, without synchronization, performing the above-described steps D1 to D4, it is possible to form a SiOCN film having a predetermined composition and a predetermined film thickness on the wafer **200**, that is, on the SiN film formed on the wafer **200** by performing the first film formation.

(108) In the second film formation, in the process of forming the SiOCN film, it is possible to supply a portion of the O component supplied to the wafer **200** or a portion of the O component contained in the SiOCN layer formed on the wafer **200** to the SiN film which is the base of the second film formation. Accordingly, since the O component can be diffused and added into the SiN film that is the base of the second film formation, it is possible to modify (oxidize) this SiN film into a SiON film having a lower dielectric constant than the SiN film. As a result, as shown in FIG. 7D, it is possible to form a laminated film in which the SiON film and the SiOCN film having low dielectric constants are laminated in this order, on the wafer **200**, that is, on the W film exposed on the wafer **200**. This laminated film becomes a so-called low dielectric constant film (low-k film).

(109) When the second film formation is performed, the O component that may diffuse below the SiN film, that is, to the W film side that is the base when forming the laminated film, is trapped by the SiN film, that is, as the SiN film itself is oxidized, so that its diffusion to the W film side is blocked. By limiting the diffusion of the O component into the W film by the SiN film in this way, it is possible to suppress re-oxidation of the W film from which the WO layer has been removed by the temperature rise of the wafer **200** under the H.sub.2 gas atmosphere. In the present disclosure,

the effect of blocking the diffusion of the O component into the W film, which is obtained by the SiN film, that is, the effect of suppressing the oxidation of the W film, is also referred to as an oxidation-blocking effect.

(110) The thickness of the SiOCN film formed in the second film formation may be thicker than the thickness of the SiN film formed in the first film formation. That is, the thickness of the SiN film formed in the first film formation may be thinner than the thickness of the SiOCN film formed in the second film formation. By doing so, when the second film formation is performed, it is possible to oxidize the entire SiN film formed in the first film formation to be modified into the SiON film, which makes it possible to modify the entire SiN film formed in the first film formation into a low dielectric constant film. As a result, it is possible to reduce the total dielectric constant of the laminated film in which the first film and the second film are laminated. Further, by making the thickness of the SiOCN film having a lower dielectric constant than the SiON film thicker than the thickness of the SiON film, that is, by making the thickness of the SiON film having a higher dielectric constant than the SiOCN film thinner than the thickness of the SiOCN film, it is possible to reduce the average dielectric constant of the laminated film in which the SiOCN film and the SiON film are laminated.

(111) The above-mentioned cycle may be repeated multiple times. That is, the thickness of the SiOCN layer formed when the above-mentioned cycle is performed once may be set to be smaller than a desired film thickness, and the above-mentioned cycle may be repeated multiple times until the film thickness of a SiOCN film formed by laminating SiOCN layers reaches the desired film thickness.

(112) (After-Purging and Returning to Atmospheric Pressure)

(113) After the formation of the SiOCN film as the second film and the modification of the SiN film formed as the first film into the SiON film are completed, a N.sub.2 gas as a purge gas is supplied from each of the nozzles **249a** and **249b** into the process chamber **201** and is exhausted through the exhaust port **231a**. Thus, the interior of the process chamber **201** is purged to remove a gas, reaction by-products, and the like remaining in the process chamber **201** from the interior the process chamber **201** (after-purge). After that, the internal atmosphere of the process chamber **201** is substituted with an inert gas (inert gas substitution) and the internal pressure of the process chamber **201** is returned to an atmospheric pressure (returning to atmospheric pressure).

(114) (Boat Unloading and Wafer Discharging)

(115) The seal cap **219** is moved down by the boat elevator **115** to open the lower end of the manifold **209**. In addition, the processed wafers **200** supported by the boat **217** are unloaded from the lower end of the manifold **209** to the outside of the reaction tube **203** (boat unloading). After the boat is unloaded, the shutter **219s** is moved and the lower end opening of the manifold **209** is sealed by the shutter **219s** via the O-ring **220c** (shutter close). The processed wafers **200** are unloaded out of the reaction tube **203** and are then discharged from the boat **217** (wafer discharging).

(116) (3) Effects According to the Present Embodiments

(117) According to the present embodiments, one or more effects set forth below may be achieved.

(118) (a) By performing the boat loading under the first temperature, it is possible to suppress the oxidation of the W film exposed on the surface of the wafer **200**. This makes it possible to suppress formation of a further WO layer on the surface of the W film, increase in the thickness of the already-formed WO layer, etc.

(119) (b) By performing the ramp-up+H.sub.2 pre-flow while raising the temperature of the wafer **200** to the second temperature higher than the first temperature, it is possible to remove the WO layer formed on the surface of the W film. It is also possible to prevent re-oxidation of the surface of the W film after removing the WO layer.

(120) (c) By performing the first film formation before the second film formation, when the second film formation is performed, it is possible to block the O component that may diffuse below the

SiN film, that is, the O component that may reach the W film. The diffusion-blocking action of the O component by this SiN film makes it possible to prevent the re-oxidation of the W film from which the WO layer has been removed by the ramp-up+H.sub.2 pre-flow.

(121) (d) In the second film formation, by using the second process gas including an oxidizing gas, it is possible to form the SiOCN film having a low dielectric constant on the wafer **200**.

(122) (e) By performing the second film formation, it is possible to oxidize the SiN film formed in the first film formation to form the SiON film. As a result, it is possible to make the laminated film, which is formed by laminating the first film and the second film, into a low dielectric constant film.

(123) (f) By making the thickness of the SiOCN film formed in the second film formation thicker than the thickness of the SiN film formed in the first film formation, that is, by making the thickness of the SiN layer formed in the first film formation thinner than the thickness of the SiOCN film formed in the second film formation, the oxidation of the SiN film can be promoted, which makes it possible to further lower the dielectric constant of the laminated film formed by laminating the first film and the second film. Further, by increasing the ratio of the thickness occupied by the second film having a particularly low dielectric constant to the total film thickness of the laminated film, that is, by decreasing the ratio of the thickness occupied by the first film having a higher dielectric constant than the second film to the total film thickness of the laminated film, it is possible to further lower the average dielectric constant of the laminated film.

(124) (g) As described above, according to the present embodiments, while an oxide film (the laminated film of the first film and the second film) formed on the W film is a low dielectric constant film, it is possible to suppress the oxidation of the W film which is the base of the oxide film. The laminated film formed by the method of the present embodiments can be suitably applied to, for example, a sidewall spacer, a hard mask, an etch stopper, and the like in a logic device such as a MPU, or a memory device such as a DRAM or a 3D NAND.

(125) (h) By setting the second temperature and the third temperature to the same temperature, it is not required to provide a step (temperature-rising step or temperature-falling step) of changing the temperature of the wafer **200** between the first film formation and the second film formation, which makes it possible to improve the throughput of substrate processing.

(126) (i) The effects of the present embodiments can be similarly obtained even when a precursor gas other than the HCDS gas is used, when a C-containing gas other than the C.sub.3H.sub.6 gas is used, when an O-containing gas other than the O.sub.2 gas is used, when a N- and H-containing gas other than the NH.sub.3 gas is used, when a reducing gas other than the H.sub.2 gas is used, and when an inert gas other than the N.sub.2 gas is used.

Other Embodiments

(127) The embodiments of the present disclosure have been specifically described above. However, the present disclosure is not limited to the above-described embodiments, and various changes can be made without departing from the gist of the present disclosure.

(128) In the above-described embodiments, the W film, which is an elemental metal film, is exemplified as a conductive metal-containing film exposed on the surface of the substrate, but the present disclosure is not limited to such embodiments. For example, the conductive metal-containing film exposed on the surface of the substrate may be a metal nitride film such as a titanium nitride film (TiN film) or a tungsten nitride film (WN film), or an elemental metal film such as an aluminum film (Al film), a cobalt film (Co film), a nickel film (Ni film), a platinum film (Pt film), or a copper film (Cu film). Even in these cases, the same effects as those in the above-described embodiments can be obtained. In the present disclosure, the conductive metal-containing film such as the TiN film or the W film is also simply referred to as a metal film.

(129) In the first film formation, as the first process gas (precursor gas), in addition to the above-mentioned various halosilane-based gases such as the HCDS gas, it may be possible to use, e.g., an alkylhalosilane-based gas such as a 1,1,2,2-tetrachloro-1,2-dimethyldisilane ((CH.sub.3).sub.2Si.sub.2Cl.sub.4, abbreviation: TCDMDS) gas, an alkylsilane-based gas such as a

hexamethyldisilane ((CH.sub.3).sub.3—Si—Si—(CH.sub.3).sub.3, abbreviation: HMDS) gas, or an alkylenesilane-based gas such as a 1,4-disilabutane (Si.sub.2C.sub.2H.sub.10, abbreviation: DSB) gas. For example, as a gas that promotes decomposition of the precursor gas, a H.sub.2 gas, a trichloroborane (BCl.sub.3) gas, or the like may be added to the precursor gas. Further, as the first process gas (reaction gas), in addition to the above-mentioned various reaction gases, it may be possible to use an amine-based gas such as a triethylamine ((C.sub.2H.sub.5).sub.3N, abbreviation: TEA) gas. Then, according to the gas-supplying sequences shown below, a SiN film, a silicon carbide film (SiC film), or a silicon carbonitride film (SiCN film) may be formed as the first film on the wafer **200**, that is, on a metal-element-containing film exposed on the surface of the wafer **200** and from which a native oxide film has been removed by a reduction process. Even in this case, the same effects as those in the above-described embodiments can be obtained. The alkylhalosilane-based gas, the alkylsilane-based gas, and the alkylenesilane-based gas are gases that act as a Si source and a C source, and the amine-base gas is a gas that acts as a N source and a C source.

(DCS.fwdarw.NH.sub.3)×*m*.Math.SiN

(HCDS.fwdarw.C.sub.3H.sub.6.fwdarw.NH.sub.3)×*m*.Math.SiCN

(HCDS.fwdarw.TEA)×*m*.Math.SiCN

(TCDMDS.fwdarw.NH.sub.3)×*m*.Math.SiCN

(DSB+H.sub.2)×*m*.Math.SiC

(DSB+BCl.sub.3)×*m*.Math.SiC

(130) When the SiC film or the SiCN film is formed as the first film in the first film formation, the SiC film or the SiCN film formed in the first film formation is oxidized by performing the second film formation, so as to be modified into a SiOC film or a SiOCN film, respectively. In this case, since the SiOC film and the SiOCN film have a lower dielectric constant than the SiON film, it is possible to further lower the dielectric constant of the laminated film formed by laminating the first film and the second film.

(131) In the second film formation, as the second process gas (precursor gas), in addition to the above-mentioned various halosilane-based gases such as the HCDS gas, it may be possible to use an alkylhalosilane-based gas such as a TCDMDS gas, an alkylsilane-based gas such as a HMDS gas, an alkylenesilane-based gas such as a DSB gas. Further, as the second process gas (reaction gas), in addition to the above-mentioned various reaction gases, it may be possible to use an amine-based gas such as a TEA gas. Then, according to the gas-supplying sequences shown below, a SiOCN film may be formed as the second film on the wafer **200**, that is, on the first film. Further, the type of the second process gas may be appropriately selected to form a silicon oxide film (SiO film), a silicon oxynitride film (SiON film), and a silicon oxycarbide film (SiOC film) as the second film. Even in this case, the same effects as those in the above-described embodiments can be obtained.

(HCDS.fwdarw.C.sub.3H.sub.6.fwdarw.NH.sub.3.fwdarw.O.sub.2)×*n*.Math.SiOCN

(HCDS.fwdarw.TEA.fwdarw.O.sub.2)×*n*.Math.SiOCN

(TCDMDS.fwdarw.NH.sub.3.fwdarw.O.sub.2)×*n*.Math.SiOCN

(132) Recipes used in each process may be prepared individually according to the processing contents and may be stored in the memory **121c** via a telecommunication line or the external memory **123**. Moreover, at the beginning of each process, the CPU **121a** may properly select an appropriate recipe from the recipes stored in the memory **121c** according to the processing contents. Thus, it is possible for a single substrate processing apparatus to form films of various kinds, composition ratios, qualities, and thicknesses with enhanced reproducibility. Further, it is possible to reduce an operator's burden and to quickly start each process while avoiding an operation error.

(133) The recipes mentioned above are not limited to newly-prepared ones but may be prepared, for example, by modifying existing recipes that are already installed in the substrate processing

apparatus. Once the recipes are modified, the modified recipes may be installed in the substrate processing apparatus via a telecommunication line or a recording medium storing the recipes. In addition, the existing recipes already installed in the substrate processing apparatus may be directly modified by operating the input/output device **122** of the substrate processing apparatus.

(134) The example in which a film is formed by using a batch-type substrate processing apparatus capable of processing a plurality of substrates at a time has been described in the above-described embodiments. The present disclosure is not limited to the above-described embodiments, but may be suitably applied, for example, to a case where a film is formed by using a single-wafer-type substrate processing apparatus capable of processing a single substrate or several substrates at a time. In addition, the example in which a film is formed by using a substrate processing apparatus including a hot-wall-type process furnace has been described in the above-described embodiments. The present disclosure is not limited to the above-described embodiments, but may be suitably applied to a case where a film is formed by using a substrate processing apparatus including a cold-wall-type process furnace.

(135) Even in the case of using these substrate processing apparatuses, each process may be performed according to the same processing procedures and process conditions as those in the above-described embodiments, and the same effects as those in the above-described embodiments can be achieved.

(136) The above-described embodiments may be used in proper combination. The processing procedures and process conditions used in this case may be the same as, for example, the processing procedures and process conditions of the above-described embodiments.

Examples

(137) As Samples 1 to 5, the above-described substrate processing apparatus was used to form a SiOCN film on a wafer in which a W film was exposed on the surface of the wafer according to the gas-supplying sequence shown in FIG. **6**. Before performing wafer charging and boat loading, the composition in the thickness direction of the W film in the initial state in the wafer of Samples 1 to 5 was measured by XPS, respectively. As a result of the measurement, the ratio (%) of the thickness of a W layer, which is an unoxidized portion of the W film, and the thickness of a WO layer, which is an oxidized portion of the W film, was 70:30.

(138) When preparing Sample 1, the boat loading and the ramp-up+H.sub.2 pre-flow under the first temperature were performed in this order, and then, without performing the first film formation, the second film formation was performed to directly form a SiOCN film on the W film without forming a SiN film on the W film. When preparing Samples 2 to 5, the boat loading and the ramp-up+H.sub.2 pre-flow under the first temperature were performed in this order, and then, the first film formation and the second film formation were performed in this order to form a SiN film and a SiOCN film on the W film in this order. That is, Samples 2 to 5 were prepared according to the substrate-processing sequence shown in FIG. **4**. The process conditions in each step when preparing each sample were set to predetermined conditions within the process condition range described in the above-described embodiments. The process conditions for performing the second film formation were the same conditions for each sample. The thickness of the SiN film and the SiOCN film in each sample was the thickness shown in FIG. **8**, respectively.

(139) After preparing Samples 1 to 5, the composition of the W film in Samples 1 to 5 was measured by XPS, respectively. The result is shown in FIG. **8**. As shown in FIG. **8**, in Samples 2 to 5 in which the SiN film was formed before the SiOCN film was formed, the existence of the WO layer in the W film could not be confirmed. It is considered that this is because the WO film formed on the surface of the W film in the initial state was removed by the ramp-up+H.sub.2 pre-flow and the re-oxidation of the W film when forming the SiOCN film could be avoided by the SiN film. On the other hand, in Sample 1 in which the SiN film was not formed before the SiOCN film was formed, the existence of the WO layer in the W film was confirmed. It is considered that this is because the WO film formed on the surface of the W film in the initial state was removed by the

ramp-up+H.sub.2 pre-flow, but a portion of the W film was re-oxidized when the SiOCN film was formed.

(140) According to the present disclosure, it is possible to provide a technique capable of suppressing the oxidation of a film formed on a substrate when the base of the film is a metal-element-containing film, while the film is a low dielectric constant film.

Claims

1. A method of processing a substrate, comprising: (a) loading a substrate including a conductive metal-element-containing film on a surface of the substrate into a process chamber under a first temperature; (b) supplying a reducing gas to the conductive metal-element-containing film while raising a temperature of the substrate to a second temperature higher than the first temperature in the process chamber, wherein the reducing gas performs a chemical reduction reaction; and (c) forming a first film, which contains silicon and at least one selected from the group of nitrogen and carbon, on the metal-element-containing film, by supplying a first process gas, which does not include an oxidizing gas, to the substrate under the second temperature in the process chamber.
2. The method of claim 1, further comprising: (d) forming a second film, which contains silicon, oxygen, carbon, and nitrogen, on the first film, by supplying a second process gas, which includes an oxidizing gas, to the substrate under a third temperature higher than the first temperature in the process chamber.
3. The method of claim 1, wherein the first temperature is set to a room temperature or higher and 200 degrees C. or lower.
4. The method of claim 1, wherein the first temperature is set to a room temperature or higher and 150 degrees C. or lower.
5. The method of claim 1, wherein at least one selected from the group of a hydrogen gas and a deuterium gas is used as the reducing gas.
6. The method of claim 1, wherein in (b), a native oxide film formed on a surface of the metal-element-containing film is removed by the temperature rise under a reducing gas atmosphere.
7. The method of claim 6, wherein in (b), an oxidation of the surface of the metal-element-containing film where the native oxide film has been removed is prevented.
8. The method of claim 7, wherein the second temperature is set to 500 degrees C. or higher and 800 degrees C. or lower.
9. The method of claim 7, wherein the second temperature is set to 600 degrees C. or higher and 700 degrees C. or lower.
10. The method of claim 1, wherein the first film includes at least one selected from the group of a silicon nitride film, a silicon carbide film, and a silicon carbonitride film.
11. The method of claim 1, wherein a thickness of the first film is 0.16 nm or more and 1 nm or less.
12. The method of claim 1, wherein a thickness of the first film is 0.16 nm or more and 0.48 nm or less.
13. The method of claim 1, wherein a thickness of the first film is 0.16 nm or more and 0.32 nm or less.
14. The method of claim 1, wherein the first process gas includes: a gas serving as a silicon source or a gas serving as a silicon source and a carbon source; and a gas serving as at least one selected from the group of a nitrogen source and a carbon source, and wherein in (c), a cycle which includes supplying the respective gases of the first process gas is performed a predetermined number of times.
15. The method of claim 2, wherein the first process gas includes: a gas serving as a silicon source or a gas serving as a silicon source and a carbon source; and a gas serving as at least one selected from the group of a nitrogen source and a carbon source, wherein in (c), the respective gases of the first process gas are intermittently supplied to the substrate, wherein the second process gas

includes: a gas serving as a silicon source or a gas serving as a silicon source and a carbon source; a gas serving as at least one selected from the group of a nitrogen source and a carbon source; and a gas serving as an oxygen source, and wherein in (d), the respective gases of the second process gas are intermittently and non-simultaneously supplied to the substrate.

16. The method of claim 2, wherein in (d), the first film formed in (c) is modified into a film having a dielectric constant lower than a dielectric constant of the first film before performing (d).

17. The method of claim 2, wherein in (c), a silicon carbonitride film is formed as the first film, and wherein in (d), a silicon oxycarbonitride film is formed as the second film, and the first film is modified from the silicon carbonitride film into a silicon oxycarbonitride film.

18. The method of claim 17, wherein the first process gas includes: a gas serving as a silicon source; a gas serving as a carbon source; and a gas serving as a nitrogen source, wherein in (c), the respective gases of the first process gas are intermittently supplied to the substrate, and wherein the second process gas includes: a gas serving as a silicon source; a gas serving as a carbon source; a gas serving as a nitrogen source; and a gas serving as an oxygen source, and wherein in (d), the respective gases of the second process gas are intermittently supplied to the substrate.

19. The method of claim 1, wherein the second temperature and the third temperature are set to be the same temperature.

20. A method of manufacturing a semiconductor device comprising the processing method of claim 1.

21. A substrate processing apparatus comprising: a process chamber in which a substrate is processed; a heater configured to heat the substrate in the process chamber; a reducing gas supply system configured to supply a reducing gas to the substrate in the process chamber; a first process gas supply system configured to supply a first process gas, which does not include an oxidizing gas, to the substrate in the process chamber; a transfer system configured to transfer the substrate into the process chamber; and a controller configured to be capable of controlling the heater, the reducing gas supply system, the first process gas supply system, and the transfer system so as to perform a process including: (a) loading the substrate including a conductive metal-element-containing film on a surface of the substrate into the process chamber under a first temperature; (b) supplying the reducing gas to the conductive metal-element-containing film while raising a temperature of the substrate to a second temperature higher than the first temperature in the process chamber, wherein the reducing gas performs a chemical reduction reaction; and (c) forming a first film, which contains silicon and at least one selected from the group of nitrogen and carbon, on the metal-element-containing film, by supplying the first process gas to the substrate under the second temperature in the process chamber.

22. A non-transitory computer-readable recording medium storing a program that causes, by a computer, a substrate processing apparatus to perform a process comprising: (a) loading a substrate including a conductive metal-element-containing film on a surface of the substrate into a process chamber under a first temperature; (b) supplying a reducing gas to the conductive metal-element-containing film while raising a temperature of the substrate to a second temperature higher than the first temperature in the process chamber, wherein the reducing gas performs a chemical reduction reaction; and (c) forming a first film, which contains silicon and at least one selected from the group of nitrogen and carbon, on the metal-element-containing film, by supplying a first process gas, which does not include an oxidizing gas, to the substrate under the second temperature in the process chamber.

23. The method of claim 1, wherein the first process gas includes: a gas serving as a silicon source or a gas serving as a silicon source and a carbon source; and a gas serving as at least one selected from the group of a nitrogen source and a carbon source.

24. The method of claim 1, wherein the first process gas includes: a gas serving as a silicon source; a gas serving as a carbon source; and a gas serving as a nitrogen source.

25. The method of claim 1, wherein the second temperature is set to 500 degrees C. or higher and

800 degrees C. or lower.

26. The method of claim 1, wherein the second temperature is set to 600 degrees C. or higher and 700 degrees C. or lower.
