

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12408399
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Lee; Minhyun et al.

Semiconductor device including two-dimensional semiconductor material

Abstract

Provided is a semiconductor device which use a two-dimensional semiconductor material as a channel layer. The semiconductor device includes: a gate electrode on a substrate; a gate dielectric on the gate electrode; a channel layer on the gate dielectric; and a source electrode and a drain electrode that may be electrically connected to the channel layer. The gate dielectric has a shape with a height greater than a width, and the channel layer includes a two-dimensional semiconductor material.

Inventors: Lee; Minhyun (Suwon-si, KR), Seol; Minsu (Suwon-si, KR), Cho; Yeonchoo (Seongnam-si, KR), Shin; Hyeonjin (Suwon-si, KR)

Applicant: Samsung Electronics Co., Ltd. (Suwon-si, KR)

Family ID: 72380894

Assignee: Samsung Electronics Co., Ltd. (Gyeonggi-do, KR)

Appl. No.: 18/761779

Filed: July 02, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20240363689 A1	Oct. 31, 2024

Foreign Application Priority Data

KR	10-2020-0007964	Jan. 21, 2020
----	-----------------	---------------

Related U.S. Application Data

Publication Classification

Int. Cl.: **H01L29/10** (20060101); **H01L21/02** (20060101); **H10D30/01** (20250101); **H10D30/62** (20250101); **H10D62/17** (20250101); **H10D64/00** (20250101); **H10D64/27** (20250101)

U.S. Cl.:

CPC **H10D62/292** (20250101); **H01L21/02568** (20130101); **H10D30/024** (20250101);
 H10D30/62 (20250101); **H10D30/6219** (20250101); **H10D64/118** (20250101);
 H10D64/514 (20250101);

Field of Classification Search

CPC: H10D (62/292); H10D (30/024); H10D (30/62); H10D (30/6219); H10D (64/118); H10D
 (64/514); H10D (30/69); H10D (30/701); H10D (30/47); H10D (64/689); H10D (64/517);
 H10D (62/882); H10D (62/235); H10D (64/511); H10D (64/512); H10D (84/013); H10D
 (84/0142); H10D (84/0158); H01L (21/02568); H01L (21/02527); H01L (21/02543);
 H01L (21/76898)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5196912	12/1992	Matsumoto et al.	N/A	N/A
9240478	12/2015	Chang et al.	N/A	N/A
9257508	12/2015	Lee et al.	N/A	N/A
9553199	12/2016	Hou et al.	N/A	N/A
9658186	12/2016	Yang et al.	N/A	N/A
9711647	12/2016	van Dal et al.	N/A	N/A
9768313	12/2016	Yeh et al.	N/A	N/A
10056498	12/2017	Yeh et al.	N/A	N/A
10084066	12/2017	Lin et al.	N/A	N/A
10269791	12/2018	Yeo et al.	N/A	N/A
10269981	12/2018	Chen et al.	N/A	N/A
2007/0138476	12/2006	Chae et al.	N/A	N/A
2013/0193412	12/2012	Lee et al.	N/A	N/A
2015/0091009	12/2014	Yamazaki et al.	N/A	N/A
2016/0365459	12/2015	Hong et al.	N/A	N/A
2017/0003248	12/2016	Yang et al.	N/A	N/A
2018/0182849	12/2017	Alian et al.	N/A	N/A
2018/0182898	12/2017	Moroz et al.	N/A	N/A
2019/0295276	12/2018	Blonde et al.	N/A	N/A
2020/0006573	12/2019	Lilak et al.	N/A	N/A
2020/0343379	12/2019	Sharma et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
103227201	12/2012	CN	N/A
106328708	12/2016	CN	N/A
2620981	12/2012	EP	N/A
2011192843	12/2010	JP	N/A
2013/0086808	12/2012	KR	N/A
20170004676	12/2016	KR	N/A
101878741	12/2017	KR	N/A

OTHER PUBLICATIONS

Hyun Gu Kim et al., “Atomic Layer Deposition on 2D Materials” American Chemical Society, Chem. Mater. 2017, 29, 3809-3826. cited by applicant

Rui Cheng et al, “Few-layer molybdenum disulfide transistors and circuits for high-speed flexible electronics” Nature Communications, Published Oct. 8, 2014, pp. 1-9. cited by applicant

Zhihao Yu et al, “Analyzing the Carrier Mobility in Transition-Metal Dichalcogenide MoS₂ Field-Effect Transistors” Wiley-VCH Verlag GmbH & Co. KGaA, Weinheim, Adv. Funct. Mater. 2017, pp. 1-17. cited by applicant

Kibum Kang et al, “High-mobility three-atom-thick semiconducting films with wafer-scale homogeneity” Nature, vol. 520, Apr. 30, 2015, pp. 656-660. cited by applicant

Extended European Search Report dated Mar. 3, 2021, issued in corresponding European Patent Application No. 20194364.4. cited by applicant

Korean Office Action dated Jan. 2, 2025 for corresponding Korean Patent Application No. 10-2020-0007964 and its English-language translation. cited by applicant

Chinese Office Action dated Jun. 25, 2025 for corresponding Chinese Patent Application No. 202011535102.5 and its English language translation. cited by applicant

Primary Examiner: Nguyen; Cuong B

Attorney, Agent or Firm: HARNESS, DICKEY & PIERCE, P.L.C.

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a divisional of U.S. application Ser. No. 18/055,565, filed Nov. 15, 2022, which is a continuation of U.S. application Ser. No. 16/928,508, filed Jul. 14, 2020, which claims the benefit of Korean Patent Application No. 10-2020-0007964, filed on Jan. 21, 2020, in the Korean Intellectual Property Office, the disclosure of each of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

(1) The present disclosure relates to semiconductor devices, and more particularly, to semiconductor devices which use a two-dimensional semiconductor material as a channel layer.

2. Description of Related Art

(2) Transistors are semiconductor devices having an electrical switching function and are used in various semiconductor products such as memories and driver integrated circuits (ICs). When the size of semiconductor devices is small, more semiconductor devices may be obtained from one wafer, and the driving speed of the semiconductor devices may increase. Thus, research has been intensively conducted into reducing the size of semiconductor devices.

(3) There is a limit to reducing the size of transistors such as metal oxide semiconductor field effect

transistors (MOSFETs) having a flat structure, and thus recently, fin field effect transistors (FinFETs) having a three-dimensional structure have been intensively studied for the implementation of micro devices.

SUMMARY

(4) Provided are semiconductor devices which use a two-dimensional semiconductor material as a channel layer.

(5) Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments of the disclosure.

(6) According to an embodiment, a semiconductor device includes: a substrate; a gate electrode on the substrate, the gate electrode having a shape with a height greater than a width; a gate dielectric on the gate electrode; a channel layer on the gate dielectric, the channel layer including a two-dimensional semiconductor material; and a source electrode and a drain electrode that may be electrically connected to the channel layer.

(7) In some embodiments, the substrate may include an insulating material. The substrate may further include a semiconductor material.

(8) In some embodiments, the gate electrode may have a height/width ratio that is greater than about 1 but less than about 20.

(9) In some embodiments, the gate electrode may include a metallic material or a conductive oxide.

(10) In some embodiments, the gate electrode may include a conductive layer and a dielectric provided in the conductive layer.

(11) In some embodiments, the gate dielectric may include a high-k material, a ferroelectric material, or both the high-k material and the ferroelectric material. The gate dielectric may include a charge trapping material.

(12) In some embodiments, the two-dimensional semiconductor material may include, for example, graphene, black phosphorus, a transition metal dichalcogenide (TMD), or a combination thereof.

(13) In some embodiments, the channel layer may have a thickness of about 10 nm or less (e.g., greater than 0 nm and less than or equal to 10 nm).

(14) In some embodiments, the source electrode and the drain electrode may overlap the gate electrode.

(15) In some embodiments, the gate dielectric may include a first dielectric and a second dielectric. The first dielectric may extend from a first end portion of the gate electrode. The second dielectric may extend from a second end portion of the gate electrode. The source and drain electrodes may overlap the first dielectric and the second dielectric, respectively.

(16) In some embodiments, the semiconductor device may further include an interconnect in the substrate and the interconnect may be electrically connected to the gate electrode.

(17) In some embodiments, the semiconductor device may further include an interconnect on an upper portion of the gate electrode and the interconnect may be electrically connected to the gate electrode.

(18) According to an embodiment, a semiconductor device includes: a substrate; a plurality of gate electrodes on the substrate, each of the plurality of gate electrodes having a shape with a height greater than a width; a connection electrode on the substrate, the connection electrode connecting the plurality of gate electrodes to each other; a plurality of gate dielectrics on the plurality of gate electrodes; a plurality of channel layers on the plurality of gate dielectrics, the plurality of channel layers including a two-dimensional semiconductor material; and a source electrode and a drain electrode that may be electrically connected to the plurality of channel layers.

(19) In some embodiments, the plurality of gate electrodes may be arranged side by side with each other.

(20) In some embodiments, the connection electrode may be provided in one piece with the plurality of gate electrodes.

- (21) In some embodiments, the semiconductor device may further include an interconnect electrically connected to the connection electrode. The interconnect may be in contact with the connection electrode between the plurality of channel layers.
- (22) In some embodiments, the two-dimensional semiconductor material may include, for example, graphene, black phosphorus, a transition metal dichalcogenide (TMD), or a combination thereof.
- (23) According to an embodiment, a semiconductor device includes: a substrate; a gate electrode on an upper surface of the substrate; a gate dielectric on the substrate, the gate dielectric including a portion covering the gate electrode and having a shape with a height greater than a width; a channel layer on the gate electric and the gate electrode, the channel layer comprising a two-dimensional semiconductor material; and a source electrode and a drain electrode electrically connected to the channel layer.
- (24) In some embodiments, the substrate may include an insulating material.
- (25) In some embodiments, the two-dimensional semiconductor material may include graphene, black phosphorus, a transition metal dichalcogenide (TMD), or a combination thereof.
- (26) In some embodiments, the channel layer may have a thickness of greater than 0 nm and about 10 nm or less.
- (27) In some embodiments, a ratio of the height of the gate electrode to a width of the gate electrode may be greater than about 1 and less than about 20.
-

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) The above and other aspects, features, and effects of embodiments of inventive concepts will be more apparent from the following description taken in conjunction with the accompanying drawings, in which:
- (2) FIG. 1 is a perspective view illustrating a semiconductor device according to an example embodiment;
- (3) FIG. 2 is a cross-sectional view taken along line A-A' of FIG. 1;
- (4) FIG. 3 is a cross-sectional view taken along line B-B' of FIG. 1;
- (5) FIG. 4 is a view illustrating a modification of a gate electrode that may be employed in the semiconductor device shown in FIG. 1;
- (6) FIG. 5 is a view illustrating another modification of the gate electrode that may be employed in the semiconductor device shown in FIG. 1;
- (7) FIG. 6 is a cross-sectional view illustrating a semiconductor device according to another example embodiment;
- (8) FIG. 7 is a cross-sectional view illustrating a semiconductor device according to another example embodiment;
- (9) FIG. 8 is a perspective view illustrating a semiconductor device according to another example embodiment;
- (10) FIG. 9 is a cross-sectional view taken along line C-C' of FIG. 8;
- (11) FIG. 10 is a perspective view illustrating a semiconductor device according to another example embodiment;
- (12) FIG. 11 is a cross-sectional view taken along line D-D' of FIG. 10;
- (13) FIG. 12 is a perspective view illustrating a semiconductor device according to another example embodiment;
- (14) FIG. 13 is a cross-sectional view taken along line E-E' of FIG. 12;
- (15) FIG. 14 is a view illustrating a modification of a gate electrode that may be employed in the semiconductor device shown in FIGS. 1 and 7;
- (16) FIG. 15 is a view illustrating a modification of a gate electrode that may be employed in the

semiconductor device shown in FIGS. 5 and 7; and

(17) FIG. 16 is a view illustrating a modification of a gate electrode that may be employed in the semiconductor device shown in FIGS. 12-13.

DETAILED DESCRIPTION

(18) Reference will now be made in detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the figures, to explain aspects. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list. For example, “at least one of A, B, and C,” “at least one of A, B, or C,” “one of A, B, C, or a combination thereof,” and “one of A, B, C, and a combination thereof,” respectively, may be construed as covering any one of the following combinations: A; B; A and B; A and C; B and C; and A, B, and C.”

(19) When the terms “about” or “substantially” are used in this specification in connection with a numerical value, it is intended that the associated numerical value includes a manufacturing or operational tolerance (e.g., $\pm 10\%$) around the stated numerical value. Moreover, when the words “generally” and “substantially” are used in connection with geometric shapes, it is intended that precision of the geometric shape is not required but that latitude for the shape is within the scope of the disclosure. Further, regardless of whether numerical values or shapes are modified as “about” or “substantially,” it will be understood that these values and shapes should be construed as including a manufacturing or operational tolerance (e.g., $\pm 10\%$) around the stated numerical values or shapes unless the context indicates otherwise.

(20) Hereinafter, example embodiments will be described with reference to the accompanying drawings. In the drawings, like reference numerals refer to like elements, and the sizes of elements may be exaggerated for clarity of illustration. The embodiments described herein are for illustrative purposes only, and various modifications may be made therein.

(21) In the following description, when an element is referred to as being “above” or “on” another element, it may be directly on the other element while making contact with the other element or may be above the other element without making contact with the other element. The terms of a singular form may include plural forms unless otherwise mentioned. It will be further understood that the terms “comprises” and/or “comprising” used herein specify the presence of stated features or elements, but do not preclude the presence or addition of one or more other features or elements.

(22) An element referred to with the definite article or a demonstrative pronoun may be construed as the element or the elements even though it has a singular form. Operations of a method may be performed in appropriate order unless explicitly described in terms of order or described to the contrary. That is, operations are not limited to the order in which the operations are described.

(23) In the present disclosure, terms such as “unit” or “module” may be used to denote a unit that has at least one function or operation and is implemented with hardware, software, or a combination of hardware and software.

(24) Furthermore, line connections or connection members between elements depicted in the drawings represent functional connections and/or physical or circuit connections by way of example, and in actual applications, they may be replaced or embodied with various additional functional connections, physical connections, or circuit connections.

(25) Examples are just used herein to describe technical ideas and should not be considered for purposes of limitation unless defined by the claims.

(26) FIG. 1 is a perspective view illustrating a semiconductor device 100 according to an example embodiment. FIG. 2 is a cross-sectional view taken along line A-A' of FIG. 1, and FIG. 3 is a cross-sectional view taken along line B-B' of FIG. 1. The semiconductor device 100 illustrated in

FIGS. 1 to 3 may include a Fin field effect transistor (FinFET).

(27) Referring to FIGS. 1 to 3, the semiconductor device **100** includes a gate electrode **130**, a gate dielectric **120**, a channel layer **140**, a source electrode **150**, and a drain electrode **160**. The gate electrode **130** may be provided on a substrate **110**. The substrate **110** may include, for example, an insulating substrate. In addition, the substrate **110** may include a semiconductor substrate (not shown) having an insulating layer formed on a surface thereof. The semiconductor substrate **110** may include, for example, silicon (Si), germanium (Ge), SiGe, or a Group III-V semiconductor material. However, the substrate **110** is not limited thereto. For example, the substrate **110** may include a silicon substrate having a silicon oxide formed on a surface thereof.

(28) The gate electrode **130** is provided on an upper surface of the substrate **110**. The gate electrode **130** may have a fin shape. The gate electrode **130** may have a width W , a height H , and a length. FIG. 1 illustrates the width W of the gate electrode **130** defined in an x-axis direction, the height H of the gate electrode **130** defined in a z-axis direction, and the length of the gate electrode **130** defined in a y-axis direction.

(29) The gate electrode **130** is shaped such that the height H of the gate electrode **130** is greater than the width W of the gate electrode **130**. That is, the ratio of the height H to the width W of the gate electrode **130**, that is, the aspect ratio of the gate electrode **130**, may be greater than about 1 (e.g., in a range of about 1 to about 5, about 1 to about 10, about 1 to about 20, but not limited thereto). In addition, the ratio of the height H to the width W of the gate electrode **130** may be less than about 20, but is not limited thereto.

(30) The gate electrode **130** may have, for example, a rectangular cross-section. In this case, the gate electrode **130** may be arranged substantially perpendicular to a surface of the substrate **110**. Here, the expression “substantially perpendicular” refers to exactly perpendicular or nearly perpendicular.

(31) The gate electrode **130** may include a metallic material or a conductive oxide. Here, the metallic material may include, for example, at least one of (or selected from the group consisting of) gold (Au), titanium (Ti), TiN, TaN, tungsten (W), molybdenum (Mo), WN, platinum (Pt), and nickel (Ni). In addition, the conductive oxide may include, for example, indium tin oxide (ITO), indium zinc oxide (IZO), or the like. However, these materials are merely examples.

(32) The gate dielectric **120** may be provided on the gate electrode **130**. The gate dielectric **120** may be provided on the upper surface of the substrate to cover the surface of the gate electrode **130**. The gate dielectric **120** may be formed by depositing an insulating material on the upper surface of the substrate **110** to cover the gate electrode **130** by, for example, chemical vapor deposition (CVD), atomic layer deposition (ALD), or physical vapor deposition (PVD).

(33) The gate dielectric **120** may include, for example, a high- k dielectric material (e.g., a material having a dielectric constant that is greater than a dielectric constant of silicon oxide). For example, the gate dielectric **120** may include an aluminum oxide, a hafnium oxide, a zirconium-hafnium oxide, a lanthanum oxide, or the like, but is not limited thereto.

(34) The gate dielectric **120** may include a ferroelectric material. The ferroelectric material has a spontaneous dipole (electric dipole), that is, a spontaneous polarization, in a crystallized material structure because the charge distribution in a unit cell is non-centrosymmetric. Thus, the ferroelectric material has a residual polarization due to dipoles even when no external electric field is applied to the ferroelectric material. In addition, the direction of polarization may be switched on a domain basis by an external electric field. The ferroelectric material may include, for example, at least one oxide of (or selected from the group consisting of) hafnium (Hf), silicon (Si), aluminum (Al), zirconium (Zr), yttrium (Y), lanthanum (La), gadolinium (Gd), and strontium (Sr). However, these materials are examples. In addition, the ferroelectric material may further include a dopant if necessary or desired.

(35) The semiconductor device **100** in which the gate dielectric **120** includes a ferroelectric material may be applied to, for example, a logic device or a memory device. When the gate

dielectric **120** includes a ferroelectric material as described above, the subthreshold swing (SS) of the semiconductor device **100** may be lowered by the negative capacitance effect, thereby improving the performance of the semiconductor device **100** and reducing the size of the semiconductor device.

(36) The gate dielectric **120** may have a multilayer structure including a high-k material and a ferroelectric material. In addition, the gate dielectric **120** may include a charge trapping layer such as a silicon nitride layer, and in this case, the semiconductor device **100** may have memory characteristics.

(37) The channel layer **140** is provided on the gate dielectric **120**. Here, the channel layer **140** is provided on the gate dielectric **120** which covers the gate electrode **130**. The channel layer **140** may include a two-dimensional semiconductor material. The term “two-dimensional semiconductor material” refers to a semiconductor material having a two-dimensional crystal structure, which may have a monolayer or multilayer structure. Each layer of the two-dimensional semiconductor material may have an atomic level thickness. In the present embodiment, the two-dimensional semiconductor material of the channel layer **140** may have a thickness of greater than 0 nm and about 10 nm or less. However, the two-dimensional semiconductor material is not limited thereto.

(38) The two-dimensional semiconductor material has good electrical characteristics, and even when the two-dimensional semiconductor material has a nanoscale thickness, the two-dimensional semiconductor material does not show large variations in the characteristics thereof and maintains high mobility such that the two-dimensional semiconductor material may be applied to various devices.

(39) The two-dimensional semiconductor material may include, for example, at least one of (or selected from the group consisting of) graphene, black phosphorus, and a transition metal dichalcogenide (TMD). Graphene is a material having a hexagonal honeycomb structure in which carbon atoms are two-dimensionally bonded, and compared to silicon (Si), graphene has high electrical mobility, good thermal properties, chemical stability, and a large surface area. In addition, black phosphorus is a material in which black phosphorus atoms are two-dimensionally bonded.

(40) For example, the TMD may include: a transition metal selected from molybdenum (Mo), tungsten (W), niobium (Nb), vanadium (V), tantalum (Ta), titanium (Ti), zirconium (Zr), hafnium (Hf), technetium (Tc), or rhenium (Re); and a chalcogen selected from sulfur (S), selenium (Se), or tellurium (Te). The TMD may be expressed as, for example, $\text{MX}_{\text{sub}2}$ where M refers to a transition metal, and X refers to a chalcogen. For example, M may be molybdenum (Mo), tungsten (W), niobium (Nb), vanadium (V), tantalum (Ta), titanium (Ti), zirconium (Zr), hafnium (Hf), technetium (Tc), rhenium (Re), or the like, and X may be sulfur (S), selenium (Se), tellurium (Te), or the like. Thus, for example, the TMD may include $\text{MoS}_{\text{sub}2}$, $\text{MoSe}_{\text{sub}2}$, $\text{MoTe}_{\text{sub}2}$, $\text{WS}_{\text{sub}2}$, $\text{WSe}_{\text{sub}2}$, $\text{WTe}_{\text{sub}2}$, $\text{ZrS}_{\text{sub}2}$, $\text{ZrSe}_{\text{sub}2}$, $\text{HfS}_{\text{sub}2}$, $\text{HfSe}_{\text{sub}2}$, $\text{NbSe}_{\text{sub}2}$, $\text{ReSe}_{\text{sub}2}$, or the like. Alternatively, the TMD may not be expressed as $\text{MX}_{\text{sub}2}$. In this case, for example, the TMD may include CuS which is a compound of a transition metal, copper (Cu), and a chalcogen, sulfur (S). Alternatively, the TMD may be a chalcogenide including a non-transition metal. The non-transition metal may include, for example, gallium (Ga), indium (In), tin (Sn), germanium (Ge), lead (Pb), or the like. In this case, the TMD may include: a compound of a non-transition metal such as gallium (Ga), indium (In), tin (Sn), germanium (Ge), or lead (Pb), and a chalcogen such as sulfur (S), selenium (Se), or tellurium (Te). For example, the TMD may include $\text{SnSe}_{\text{sub}2}$, GaS, GaSe, GaTe, GeSe, $\text{In}_{\text{sub}2}\text{Se}_{\text{sub}3}$, $\text{InSnS}_{\text{sub}2}$, or the like.

(41) As described above, the TMD may include: a metal element selected from molybdenum (Mo), tungsten (W), niobium (Nb), vanadium (V), tantalum (Ta), titanium (Ti), zirconium (Zr), hafnium (Hf), technetium (Tc), rhenium (Re), copper (Cu), gallium (Ga), indium (In), tin (Sn), germanium (Ge), or lead (Pb); and a chalcogen selected from sulfur (S), selenium (Se), or tellurium (Te).

However, the materials mentioned above are merely examples, and examples of the TMD may include other materials which are not mentioned above.

- (42) The two-dimensional semiconductor material may be doped with a p-type dopant or an n-type dopant to control mobility. Here, for example, a p-type dopant and an n-type dopant used for graphene or carbon nanotubes (CNTs) may be used as the p-type dopant and the n-type dopant. The p-type dopant or the n-type dopant may be implanted by an ion implantation method or a chemical doping method.
- (43) Examples of a source of the p-type dopant may include: ionic liquids such as NO₂BF₄, NOBF₄, or NO₂SbF₆; acidic compounds such as HCl, H₂PO₄, CH₃COOH, H₂SO₄, or HNO₃; and organic compounds such as dichlorodicyanoquinone (DDQ), Oxone, dimyristoylphosphatidylinositol (DMPI), or trifluoromethanesulfonimide. Other examples of the source of the p-type dopant may include HPtCl₄, AuCl₃, HAuCl₄, AgOTf (silver trifluoromethanesulfonate), AgNO₃, H₂PdCl₆, Pd(OAc)₂, and Cu(CN)₂.
- (44) Examples of a source of the n-type dopant may include: a reduction product of a substituted or unsubstituted nicotinamide; a reduction product of a compound which is chemically bound to a substituted or unsubstituted nicotinamide; and a compound including at least two pyridinium moieties in which a nitrogen atom of at least one of the pyridinium moieties is reduced. For example, the source of the n-type dopant may include nicotinamide mononucleotide-H (NMNH), nicotinamide adenine dinucleotide-H (NADH), nicotinamide adenine dinucleotide phosphate-H (NADPH), or viologen. Alternatively, the source of the n-type dopant may include a polymer such as polyethylenimine (PEI). Alternatively, the n-type dopant may include an alkali metal such as potassium (K) or lithium (Li). The above-listed p-type dopant materials and n-type dopant materials are examples. That is, other materials may be used as the p-type dopant and the n-type dopant.
- (45) The channel layer **140** may be formed by depositing a two-dimensional semiconductor material on the gate dielectric **120** by a method such as metal organic CVD (MOCVD) or ALD, and patterning the two-dimensional semiconductor material.
- (46) The source electrode **150** and the drain electrode **160** are provided on both sides of the channel layer **140**, respectively. Here, the source electrode **150** and the drain electrode **160** are in contact with the channel layer **140** and are electrically connected to the channel layer **140**. In this case, the source electrode **150** and the drain electrode **160** may overlap the gate electrode **130**. The source electrode **150** and the drain electrode **160** may include, for example, a metallic material having high electrical conductivity, such as silver (Ag), gold (Au), platinum (Pt), or copper (Cu), but are not limited thereto.
- (47) When the thickness of silicon (Si) of a Si-based FinFET is several nanometers (nm) or less, the number of carriers in the silicon reduces, and thus electron mobility reduces. In the present embodiment, however, the channel layer **140** includes a two-dimensional semiconductor material, and thus even when the thickness of the channel layer **140** is several nanometers (nm) or less, high electron mobility may be maintained. Therefore, a high-performance semiconductor device having a fine size, for example, a FinFET having a fine channel width within the range of about 10 nm or less (e.g., greater than 0 nm and less than or equal to 10 nm) may be realized.
- (48) A high Schottky Barrier may be formed between the channel layer **140** including a two-dimensional semiconductor material and the source and drain electrodes **150** and **160**, and thus contact resistance may increase. In the present embodiment, the gate electrode **130** having a fin shape overlaps the source and drain electrodes **150** and **160** such that the Schottky barrier formed between the channel layer **140** including a two-dimensional semiconductor material and the source and drain electrodes **150** and **160** may be reduced by a gating effect, and thus on-current may be increased.
- (49) FIG. 4 is a view illustrating a modification of the gate electrode **130** that may be employed in the semiconductor device **100** shown in FIG. 1.
- (50) Referring to FIG. 4, a gate electrode **131** may have a trapezoidal cross-section. In this case, the

gate electrode **131** is shaped such that the height of the gate electrode **131** is greater than the maximum width of the gate electrode **131**. That is, the ratio of the height to the maximum width of the gate electrode **131** may be greater than about 1 (e.g., in a range of about 1 to about 5, about 1 to about 10, about 1 to about 20, but not limited thereto). The gate electrode **131** may be arranged substantially perpendicular to the surface of the substrate **110**. For example, the angle θ between an outer wall surface **131'** of the gate electrode **131** and the surface of the substrate **110** may be, for example, greater than about 60 degrees but less than about 90 degrees.

(51) In some embodiments, as depicted in FIG. **14**, the semiconductor device in FIG. **4** may be further modified to include an interconnect **345** in the substrate **110** and electrically connected to the gate electrode **131** to apply an electrical signal to the gate electrode **131**. For example, the interconnect **345** may be provided in the substrate **110** such that the interconnect **145** may be in contact with a lower surface of the gate electrode **131**. The interconnect **345** may be formed by filling a conductive material in a through-hole formed in the substrate **110**. The interconnect **345** may include, for example, a conductive material such as cobalt (Co) or tungsten (W). However, the interconnect **345** is not limited thereto, and examples of the conductive material may include various other materials.

(52) FIG. **5** is a view illustrating another modification of the gate electrode **130** that may be employed in the semiconductor device **100** shown in FIG. **1**.

(53) Referring to FIG. **5**, a gate electrode **132** may include a conductive layer **132b** and a dielectric **132a** provided in the conductive layer **132b**. The ratio of the height to the maximum width of the gate electrode **132** may be greater than about 1 (e.g., in a range of about 1 to about 5, about 1 to about 10, about 1 to about 20, but not limited thereto). Here, the conductive layer **132b** may cover the surface of the dielectric **132a**. The conductive layer **132b** may include a metallic material or a conductive oxide. Here, the metallic material may include, for example, at least one of (or selected from the group consisting of) gold (Au), titanium (Ti), TiN, TaN, tungsten (W), molybdenum (Mo), WN, platinum (Pt), and nickel (Ni), and the conductive oxide may include, for example, ITO, IZO, or the like. In addition, Examples of the dielectric **132a** may include various insulating materials.

(54) FIG. **6** is a cross-sectional view illustrating a semiconductor device **200** according to another example embodiment.

(55) Referring to FIG. **6**, in the semiconductor device **200**, a pin-shaped gate electrode **230** is provided on an upper surface of a substrate **110**, and first and second dielectrics **235** and **236** are provided on both end portions of the gate electrode **230**. The substrate **110** and the gate electrode **230** are the same as those described above, and thus descriptions thereof will not be repeated here.

(56) In the length direction (for example, a y-axis direction) of the semiconductor device **200**, the first dielectric **235** extends from an end portion of the gate electrode **230**, and the second dielectric **236** extends from the other end portion of the gate electrode **230**. Here, the first and second dielectrics **235** and **236** may include various insulating materials.

(57) A gate dielectric **220** is provided on the gate electrode **230** and the first and second dielectrics **235** and **236**. Here, the gate dielectric **220** may be provided on the upper surface of the substrate **110** to cover the surface of the gate electrode **230** and the surfaces of the first and second dielectrics **235** and **236**. In addition, a channel layer **240** including a two-dimensional semiconductor material is provided on the gate dielectric **220**. Since the gate dielectric **220** and the channel layer **240** are the same as those described above, descriptions thereof will not be repeated here.

(58) A source electrode **150** and a drain electrode **160** are respectively provided on both sides of the channel layer **240** and are electrically connected to the channel layer **240**. Here, the source electrode **150** may overlap the first dielectric **235**, and the drain electrode **160** may overlap the second dielectric **236**. Therefore, the source electrode **150** and the drain electrode **160** may not overlap the gate electrode **230**.

(59) FIG. **7** is a cross-sectional view illustrating a semiconductor device **300** according to another example embodiment. The semiconductor device **300** illustrated in FIG. **7** is the same as the

semiconductor device **100** illustrated in FIG. **1** except that an interconnect **345** is provided in a substrate **310**.

(60) Referring to FIG. **7**, a fin-shaped gate electrode **330** is provided on an upper surface of the substrate **310**, and a gate dielectric **320** is provided to cover the gate electrode **330**. In addition, a channel layer **340** including a two-dimensional semiconductor material is provided on the gate dielectric **320**. In addition, although not shown in FIG. **7**, a source electrode and a drain electrode are provided on both sides of the channel layer **340**, respectively.

(61) The source electrode and the drain electrode may overlap the gate electrode **330**. Alternatively, the source electrode and the drain electrode may not overlap the gate electrode **330**. In this case, first and second dielectrics (not shown) may extend from both end portions of the gate electrode **330**, and the source electrode and the drain electrode may respectively overlap the first and second dielectrics.

(62) The interconnect **345** may be provided in the substrate **310** and electrically connected to the gate electrode **330** to apply an electrical signal to the gate electrode **330**. For example, the interconnect **345** may be provided in the substrate **310** such that the interconnect **345** may be in contact with a lower surface of the gate electrode **330**. The interconnect **345** may be formed by filling a conductive material in a through-hole formed in the substrate **310**. The interconnect **345** may include, for example, a conductive material such as cobalt (Co) or tungsten (W). However, the interconnect **345** is not limited thereto, and examples of the conductive material may include various other materials.

(63) In some embodiments, as depicted in FIG. **15**, the semiconductor device in FIG. **7** may be further modified to include an interconnect **345** in the substrate **110** and electrically connected to the gate electrode **132** to apply an electrical signal to the gate electrode **132**. The interconnect **345** in FIG. **15** may be formed of the same materials as the interconnect **345** in FIG. **7** so a detailed description thereof is omitted.

(64) FIG. **8** is a perspective view illustrating a semiconductor device **400** according to another example embodiment. In addition, FIG. **9** is a cross-sectional view taken along line C-C' of FIG. **8**.

(65) Referring to FIGS. **8** and **9**, in the semiconductor device **400**, a fin-shaped gate electrode **430** is provided on an upper surface of a substrate **410**, and a gate dielectric **420** is provided to cover the gate electrode **430**. In addition, a channel layer **440** including a two-dimensional semiconductor material is provided on the gate dielectric **420**. Here, the substrate **410**, the gate electrode **430**, the gate dielectric **420**, and the channel layer **440** are the same as those described above, and thus descriptions thereof will not be repeated here.

(66) A source electrode **450** and a drain electrode **460** are provided on the channel layer **440** at a distance from each other. Here, the source electrode **450** and the drain electrode **460** are electrically connected to the channel layer **440**. The source electrode **450** and the drain electrode **460** may overlap the gate electrode **430**. In addition, an interconnect **445** for applying an electrical signal to the gate electrode **430** is provided on an upper portion of the gate electrode **430**.

(67) The interconnect **445** is provided on the upper portion of the gate electrode **430** at a position outside the drain electrode **460**. Here, the interconnect **445** may be in contact with an upper surface of the gate electrode **430** through the channel layer **440** and the gate dielectric **420**. The gate dielectric **420** may extend between the interconnect **445** and the channel layer **440** for electrical insulation therebetween.

(68) In the above, the case in which the interconnect **445** is provided on an upper portion of the gate electrode **430** at a position outside the drain electrode **460** is described. However, this is a non-limiting example, and in another example, the interconnect **445** may be provided on an upper portion of the gate electrode **430** at a position outside the source electrode **450**.

(69) FIG. **10** is a perspective view illustrating a semiconductor device **500** according to another example embodiment. In addition, FIG. **11** is a cross-sectional view taken along line D-D' of FIG. **10**.

(70) Referring to FIGS. **10** and **11**, in the semiconductor device **500**, a fin-shaped gate electrode **530** is provided on an upper surface of a substrate **510**, and a gate dielectric **520** is provided to cover the gate electrode **530**. In addition, a channel layer **540** including a two-dimensional semiconductor material is provided on the gate dielectric **520**.

(71) A source electrode **550** and a drain electrode **560** are provided on both sides of the channel layer **560**, respectively. The source electrode **550** and the drain electrode **560** are electrically connected to the channel layer **540**. The source electrode **550** and the drain electrode **560** may overlap the gate electrode **530**.

(72) Alternatively, the source electrode **550** and the drain electrode **560** may not overlap the gate electrode **530**. In this case, first and second dielectrics (not shown) may extend from both end portions of the gate electrode **330**, and the source electrode **550** and the drain electrode **560** may respectively overlap the first and second dielectrics.

(73) An interconnect **545** for applying an electrical signal to the gate electrode **530** is provided on an upper portion of the gate electrode **530**. The interconnect **545** is provided on the upper portion of the gate electrode **430** at a position between the source electrode **550** and the drain electrode **560**. Here, the interconnect **545** may be in contact with an upper surface of the gate electrode **530** through the channel layer **540** and the gate dielectric **520**.

(74) FIG. **12** is a perspective view illustrating a semiconductor device **600** according to another example embodiment. In addition, FIG. **13** is a cross-sectional view taken along line E-E' of FIG. **12**.

(75) Referring to FIGS. **12** and **13**, the semiconductor device **600** includes first and second gate electrodes **631** and **632**, a connection electrode **635**, first and second gate dielectrics **621** and **622**, first and second channel layers **641** and **642**, a source electrode **650**, and a drain electrode **660**.

(76) The first and second gate electrodes **631** and **632** may be provided on a substrate **610** at a distance from each other. Here, the first and second gate electrodes **631** and **632** may be arranged side by side with each other. However, the first and second gate electrodes **631** and **632** are not limited thereto. The substrate **610** may include, for example, an insulating substrate. In addition, the substrate **610** may include a semiconductor substrate (not shown) having an insulating layer formed on a surface thereof.

(77) Each of the first and second gate electrodes **631** and **632** may have a fin shape having a width, a height, and a length. Here, each of the first and second gate electrodes **631** and **632** may have a shape with a height greater than a width. For example, the first and second gate electrodes **631** and **632** may each have a height/width ratio, that is, an aspect ratio, within the range of greater than about 1 but less than or equal to about 20.

(78) Each of the first and second gate electrodes **631** and **632** may have, for example, a rectangular cross-section. In this case, each of the first and second gate electrodes **631** and **632** may be arranged substantially perpendicular to the surface of the substrate **610**. Alternatively, the first and second gate electrodes **631** and **632** may have, for example, a trapezoidal cross-section.

(79) The first and second gate electrodes **631** and **632** may include a metallic material or a conductive oxide. Here, the metallic material may include, for example, at least one of (or selected from the group consisting of) gold (Au), titanium (Ti), TiN, TaN, tungsten (W), molybdenum (Mo), WN, platinum (Pt), and nickel (Ni), and the conductive oxide may include, for example, ITO, IZO, or the like. However, these materials are merely examples.

(80) The connection electrode **635** may be provided on the substrate **610** to connect the first and second gate electrodes **631** and **632** to each other. Here, the connection electrode **635** has a function of electrically connecting the first gate electrode **631** and the second gate electrode **632** to each other. The connection electrode **635** may be formed in one piece with the first and second gate electrodes **631** and **632**. In this case, the connection electrode **635** may include the same material as the first and second gate electrodes **631** and **632**. Alternatively, the connection electrode **635** may not be formed in one piece with the first and second gate electrodes **631** and **632**.

(81) The first and second gate dielectrics **621** and **622** are respectively provided on the first and second gate electrodes **631** and **632**. The first gate dielectric **621** may cover the first gate electrode **631**, and the second gate dielectric **622** may cover the second gate electrode **632**. In this case, at least a portion of the connection electrode **635** of the first and second gate electrodes **631** and **632** is opened through the first and second gate dielectrics **621** and **622**.

(82) The first and second gate dielectrics **621** and **622** may include, for example, a high-k dielectric material. The first and second gate dielectrics **621** and **622** may include a ferroelectric material, and if necessary, the ferroelectric material may further include a dopant. In addition, the first and second gate dielectrics **621** and **622** may have a multilayer structure including a high-k material and a ferroelectric material. In addition, the first and second gate dielectrics **621** and **622** may include a charge trapping material, and in this case, the semiconductor device **600** may have memory characteristics.

(83) The first channel layer **641** is provided on the first gate dielectric **621**, and the second channel layer **642** is provided on the second gate dielectric **622**. The first channel layer **641** is provided on the first gate dielectric **621** covering the first gate electrode **631**, and the second channel layer **642** is provided on the second gate dielectric **622** covering the second gate electrode **632**.

(84) The first and second channel layers **641** and **642** may include a two-dimensional semiconductor material. Here, the two-dimensional semiconductor material may have a monolayer or multilayer structure. The two-dimensional semiconductor material of the first and second channel layers **641** and **642** may have a thickness of about 10 nm or less, but is not limited thereto.

(85) The two-dimensional semiconductor material may include, for example, at least one of (or selected from the group consisting of) graphene, black phosphorus, and a TMD. Here, the TMD may include: a metal element selected from molybdenum (Mo), tungsten (W), niobium (Nb), vanadium (V), tantalum (Ta), titanium (Ti), zirconium (Zr), hafnium (Hf), technetium (Tc), rhenium (Re), copper (Cu), gallium (Ga), indium (In), tin (Sn), germanium (Ge), or lead (Pb); and a chalcogen selected from sulfur (S), selenium (Se), or tellurium (Te). The two-dimensional semiconductor material may be doped with a p-type dopant or an n-type dopant to control mobility.

(86) The source and drain electrodes **650** and **660** are respectively provided on both sides of the first and second channel layers **641** and **642**. Here, the source electrode **650** may be provided on sides of the first and second channel layers **641** and **642**, and the drain electrode **660** may be provided on the other sides of the first and second channel layers **641** and **642**. The source and drain electrodes **650** and **660** may include a metallic material having high electrical conductivity.

(87) The source and drain electrodes **650** and **660** may overlap the first and second gate electrodes **631** and **632**. Alternatively, the source and drain electrodes **650** and **660** may not overlap the first and second gate electrodes **631** and **632**. In this case, first and second dielectrics (not shown) may extend from both end portions of each of the first and second gate electrodes **631** and **632**, and the source and drain electrodes **650** and **660** may overlap the first and second dielectrics.

(88) An interconnect **645** may be provided on an upper portion of the connection electrode **635** and electrically connected to the connection electrode **635**. The interconnect **645** may apply an electrical signal to the first and second gate electrodes **631** and **632** through the connection electrode **635**. The interconnect **645** may be in contact with an upper surface of the connection electrode **635** which is opened through the first and second gate dielectrics **621** and **622**. Here, the interconnect **645** may be positioned between the source electrode **650** and the drain electrode **660**.

(89) An insulating layer **670** may be further provided on the substrate **610** such that the semiconductor device **600** may be embedded in the insulating layer. Here, the insulating layer **670** may include, for example, a low-k dielectric material, but is not limited thereto. In the above, the case in which the interconnect **645** is positioned between the source electrode **650** and the drain electrode **660** has been described. However, embodiments are not limited thereto, and the interconnect **645** may be provided outside the source electrode **650** or the drain electrode **660**.

(90) In the above, the case in which two fin-shaped gate electrodes **631** and **632** are provided on the

substrate **610** has been described. However, embodiments are not limited thereto, and three or more gate electrodes may be provided on the substrate **610**. In this case, connection electrodes may be provided between the gate electrodes, and interconnects may be electrically connected to the connection electrodes.

(91) FIG. **16** is a view illustrating a modification of a gate electrode that may be employed in the semiconductor device shown in FIGS. **12-13**.

(92) Referring to FIG. **16**, a semiconductor device **600'** according to example embodiments may be the same as the semiconductor device **600** in FIGS. **12-13**, except the interconnect **645'** may extend through the substrate **610** and contact a bottom surface of the connection electrode **635**. The interconnect **645'** may be formed of the same materials described above for the interconnect **645** in FIGS. **12-13** so a detailed description thereof is omitted.

(93) In addition, a plurality of such semiconductor devices as described above may be arranged horizontally or vertically. Although embodiments have been described, the embodiments are for illustrative purposes only, and those skilled in the art may make various modifications therefrom.

(94) As described above, when the thickness of silicon of a Si-based FinFET is several nanometers (nm) or less, the number of carriers in the silicon reduces, and thus electron mobility reduces. In the semiconductor devices of the example embodiments, however, the channel layers include a two-dimensional semiconductor material, and thus even when the channel layers have a thickness of several nanometers (nm) or less, the channel layers may maintain high electron mobility. Therefore, the semiconductor devices may be implemented as high-performance semiconductor devices having a fine size, for example, FinFETs having a fine channel width within the range of greater than 0 nm and about 10 nm or less.

(95) It should be understood that embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments. While one or more embodiments have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of inventive concepts as defined by the following claims.

Claims

1. A semiconductor device comprising: a substrate; a plurality of gate electrodes on the substrate, each of the plurality of gate electrodes having a shape with a height greater than a width; a connection electrode on the substrate, the connection electrode connecting the plurality of gate electrodes to each other; a plurality of gate dielectrics on the plurality of gate electrodes; a plurality of channel layers on the plurality of gate dielectrics, the plurality of channel layers comprising a two-dimensional semiconductor material; and a source electrode and a drain electrode that are electrically connected to the plurality of channel layers.
2. The semiconductor device of claim 1, wherein the plurality of gate electrodes are arranged side by side with each other.
3. The semiconductor device of claim 1, wherein the connection electrode is provided in one piece with the plurality of gate electrodes.
4. The semiconductor device of claim 1, further comprising: an interconnect electrically connected to the connection electrode.
5. The semiconductor device of claim 4, wherein the interconnect contacts the connection electrode between the plurality of channel layers.
6. The semiconductor device of claim 5, wherein the plurality of gate dielectrics include a first gate dielectric and a second gate dielectric, and a portion of an upper surface of the connection electrode is opened through the first gate dielectric and the second gate dielectric to provide an opened

portion of the upper surface of the connection electrode.

7. The semiconductor device of claim 6, wherein the interconnect contacts the opened portion of the upper surface of the connection electrode.

8. The semiconductor device of claim 7, wherein the interconnect is positioned between the source electrode and the drain electrode.

9. The semiconductor device of claim 5, wherein a portion of a lower surface of the connection electrode is opened through the substrate to provide an opened portion of the lower surface of the connection electrode.

10. The semiconductor device of claim 9, wherein the interconnect contacts the opened portion of the lower surface of the connection electrode.

11. The semiconductor device of claim 1, wherein the two-dimensional semiconductor material comprises graphene, black phosphorus, a transition metal dichalcogenide (TMD), or a combination thereof.

12. The semiconductor device of claim 1, wherein the two-dimensional semiconductor material has a monolayer structure or a multilayer structure.

13. The semiconductor device of claim 1, wherein each of the plurality of channel layers has a thickness of greater than 0 nm and about 10 nm or less.

14. The semiconductor device of claim 1, wherein the substrate comprises an insulating material.

15. The semiconductor device of claim 14, wherein the substrate further comprises a semiconductor material.

16. The semiconductor device of claim 1, wherein each of the plurality of gate electrodes has a height/width ratio that is greater than about 1 but less than about 20.

17. The semiconductor device of claim 1, wherein each of the plurality of gate electrodes comprises a metallic material or a conductive oxide.

18. The semiconductor device of claim 1, wherein each of the plurality of gate dielectrics comprises a high-k material, a ferroelectric material, or both the high-k material and the ferroelectric material.

19. The semiconductor device of claim 1, wherein each of the plurality of gate dielectrics comprises a charge trapping material.

20. The semiconductor device of claim 1, wherein the source electrode and the drain electrode overlap the plurality of gate electrodes.
