

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12386102
Kind Code	B2
Date of Patent	August 12, 2025
Inventor(s)	Uchida; Kazue et al.

Optical element, optical system, and optical apparatus

Abstract

An optical element includes a substrate and an antireflection film. The antireflection film comprises a first film formed on the substrate and a second film formed on the first film. The second film comprises a first layer, a second layer, and a third layer arranged consecutively in order from a side closer to the first film. The first layer includes magnesium fluoride. The second layer includes silicon oxide and aluminum oxide. The third layer includes a fluorine-containing organic compound.

Inventors:	Uchida; Kazue (Tochigi, JP), Ban; Masuo (Tochigi, JP)
Applicant:	CANON KABUSHIKI KAISHA (Tokyo, JP)
Family ID:	88066777
Assignee:	Canon Kabushiki Kaisha (Tokyo, JP)
Appl. No.:	18/180750
Filed:	March 08, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230296809 A1	Sep. 21, 2023

Foreign Application Priority Data

JP	2022-041285	Mar. 16, 2022
----	-------------	---------------

Publication Classification

Int. Cl.: G02B1/115 (20150101); G02B1/111 (20150101); G02B1/18 (20150101); G02B3/00 (20060101); G02B7/02 (20210101)

U.S. Cl.:

CPC **G02B1/115** (20130101); **G02B1/111** (20130101); **G02B1/18** (20150115); **G02B3/0062** (20130101); **G02B7/02** (20130101);

Field of Classification Search

CPC: G02B (1/11-115); G02B (1/18); G02B (3/00-14)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
10345489	12/2018	Fukaya	N/A	C03C 17/3452
2005/0195503	12/2004	Chen	359/819	G02B 27/0006
2012/0028005	12/2011	Zheng	427/164	C23C 14/10
2014/0329072	12/2013	Hirasawa	427/576	C23C 16/402

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2009-092746	12/2008	JP	N/A
2013/118622	12/2012	WO	N/A

OTHER PUBLICATIONS

Machine translation of JP 2009092746. Retrieved Jan. 14, 2025. cited by examiner
Dobrowolski, J.A. (eds. Bass et al.). “Chapter 42: Optical Properties of Films and Coatings”,
Handbook of Optics, vol. I: Fundamentals, Techniques, and Design, (1995); pp. 42.3 to 42.130.
cited by examiner

Primary Examiner: Khatri; Prashant J

Attorney, Agent or Firm: Canon U.S.A., Inc. IP Division

Background/Summary

BACKGROUND

Technical Field

(1) One of the aspects of the disclosure relates to an optical element, an optical system, and an optical apparatus.

Description of the Related Art

(2) Japanese Patent Laid-Open No. 2009-92746 discloses an antireflection film that includes an MgF.sub.2 layer as the outermost surface and an antifouling layer made of a fluorine-containing organic compound formed on a surface of the antireflection film. PCT International Publication No. 2013/118622 discloses an antireflection film that includes a SiO.sub.2 layer formed by a vacuum deposition method on a surface of an MgF.sub.2 layer as the outermost surface, and an antifouling film made of fluororesin provided on the surface of the SiO.sub.2 layer.

(3) The structure of the antireflection film disclosed in Japanese Patent Laid-Open No. 2009-92746 has low adhesion between the MgF.sub.2 layer and the antifouling layer, and may cause the film to

peel off. The structure of the antireflection film disclosed in PCT International Publication No. 2013/118622 has low adhesion between the MgF.sub.2 layer and the SiO.sub.2 layer because of a large tensile stress of the MgF.sub.2 layer, and may cause the film to peel off. Therefore, none of the structures of the antireflection films disclosed in Japanese Patent Laid-Open No. 2009-92746 and PCT International Publication No. 2013/118622 can provide an optical element that has high mechanical strength, environmental durability, and antifouling performance.

SUMMARY

(4) One of the aspects of the embodiment provides an optical element that can have high mechanical strength, environmental durability, and antifouling performance.

(5) An optical element according to one aspect of the disclosure includes a substrate and an antireflection film. The antireflection film comprises a first film formed on the substrate and a second film formed on the first film. The second film comprises a first layer, a second layer, and a third layer arranged consecutively in order from a side closer to the first film. The first layer includes magnesium fluoride. The second layer includes silicon oxide and aluminum oxide. The third layer includes a fluorine-containing organic compound.

(6) An optical element according to another aspect of the disclosure includes a substrate and an antireflection film. The antireflection film consists of a first film formed on the substrate and a second film formed on the first film. The second film consists of a first layer, a second layer, a third layer, and a fourth layer in order from a side closer to the first film. Each of the first layer and third layer includes silicon oxide and aluminum oxide. The second layer includes magnesium fluoride. The fourth layer includes a fluorine-containing organic compound.

(7) An optical system and an optical apparatus each including one of the above optical elements also constitute another aspect of the disclosure.

(8) Further features of the disclosure will become apparent from the following description of embodiments with reference to the attached drawings.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 is a schematic sectional view of an optical element according to each of Examples 1 to 8.

(2) FIG. 2 is a schematic sectional view of an optical element according to each of Examples 9 to 12.

(3) FIG. 3 illustrates a reflectance characteristic of the optical element according to Example 1 at an incident angle of 0 degrees.

(4) FIG. 4 illustrates a reflectance characteristic of the optical element according to Example 2 at an incident angle of 0 degrees.

(5) FIG. 5 illustrates a reflectance characteristic of the optical element according to Example 3 at an incident angle of 0 degrees.

(6) FIG. 6 illustrates a reflectance characteristic of the optical element according to Example 4 at an incident angle of 0 degrees.

(7) FIG. 7 illustrates a reflectance characteristic of the optical element according to Example 5 at an incident angle of 0 degrees.

(8) FIG. 8 illustrates a reflectance characteristic of the optical element according to Example 6 at an incident angle of 0 degrees.

(9) FIG. 9 illustrates a reflectance characteristic of the optical element according to Example 7 at an incident angle of 0 degrees.

(10) FIG. 10 illustrates a reflectance characteristic of the optical element according to Example 8 at an incident angle of 0 degrees.

(11) FIG. 11 illustrates a reflectance characteristic of the optical element according to Example 9 at

an incident angle of 0 degrees.

(12) FIG. 12 illustrates a reflectance characteristic of the optical element according to Example 10 at an incident angle of 0 degrees.

(13) FIG. 13 illustrates a reflectance characteristic of the optical element according to Example 11 at an incident angle of 0 degrees.

(14) FIG. 14 illustrates a reflectance characteristic of the optical element according to Example 12 at an incident angle of 0 degrees.

(15) FIG. 15 is a sectional view of an optical system according to Example 13.

(16) FIG. 16 is an external perspective view of the image pickup apparatus according to Example 14.

DESCRIPTION OF THE EMBODIMENTS

(17) Referring now to the accompanying drawings, a detailed description will be given of embodiments according to the disclosure.

(18) Referring now to FIG. 1, a description will be given of a schematic structure of an optical element 300 according to each of Examples 1 to 8. FIG. 1 is a schematic sectional view illustrating the optical element 300. The optical element 300 includes a substrate (base material) 200 and an antireflection film 100 formed on the substrate 200. The substrate 200 is, for example, a transparent substrate made of a resin material or a glass material. The antireflection film 100 includes a multilayer film (first film) 111 and a multilayer film (second film) 101 in order from the substrate 200. That is, the antireflection film 100 includes the multilayer film 111 formed on the substrate 200 and the multilayer film 101 formed on the multilayer film 111 (formed farthest from the substrate 200).

(19) The multilayer film 111 includes layers 11, 12, 13, 14, 15, and 16 in order from the side closer to the substrate 200. The multilayer film 111 includes, but is not limited to, six layers in this example. The multilayer film 111 may have any number of layers as long as it has one or more layers. The multilayer film 101 has three layers, a layer (first layer) 01, a layer (second layer) 02, and a layer 03 in order from the side closer to the multilayer film 111.

(20) The layer 01 includes magnesium fluoride (MgF.sub.2). The layer 02 includes silicon oxide (SiO.sub.2) and aluminum oxide (Al.sub.2O.sub.3). The silicon oxide material containing a small amount of aluminum is known to form a denser film upon vapor deposition than a material that contains no aluminum. Therefore, the layer 02 becomes a strong film with excellent scratch resistance and has a very large compressive stress. The layer 03, which is the outermost layer of the antireflection film 100, includes a fluorine-containing organic compound and has excellent water repellency and oil repellency. Therefore, water droplets and dirt that have been put on the layer 03 can be easily removed.

(21) The layers 02 and 03 are strongly adhered to each other because the silicon oxide and the fluorine-containing organic compound contained in each layer are chemically bonded. On the other hand, the layer 01 containing magnesium fluoride has a large tensile stress. In a case where the layer 01 having tensile stress and the layer 02 having compressive stress are close to each other, the respective stresses are canceled and the adhesion between the layers 01 and 02 can be improved. In the thus-structured the multilayer film 101, the film adhesion and the abrasion resistance are improved.

(22) Examples 1 to 8 may satisfy the following inequality (1):

$$\lambda/8 \leq n_{\text{sub.1}} d_{\text{sub.1}} + n_{\text{sub.2}} d_{\text{sub.2}} + n_{\text{sub.3}} d_{\text{sub.3}} \leq \lambda/2 \quad (1)$$

where $n_{\text{sub.1}}$, $n_{\text{sub.2}}$, and $n_{\text{sub.3}}$ are refractive indices for the d-line of the layers 01, 02, and 03, $d_{\text{sub.1}}$, $d_{\text{sub.2}}$, and $d_{\text{sub.3}}$ (nm) are physical film thicknesses of the layers 01, 02, and 03, respectively, and λ is a wavelength of the d-line.

(23) Inequality (1) may be replaced with inequality (1a) below:

$$\lambda/6 \leq n_{\text{sub.1}} d_{\text{sub.1}} + n_{\text{sub.2}} d_{\text{sub.2}} + n_{\text{sub.3}} d_{\text{sub.3}} \leq \lambda/3 \quad (1a)$$

(24) The antireflection film 100 improves the antireflection performance when the outermost layer

(uppermost layer) is made of a material with a lower refractive index and has an optical film thickness of about $\lambda/4$. Examples 1 to 8 satisfy inequality (1) and thereby improves the antireflection performance by regarding the multilayer film **101** as a layer substantially equivalent to the low refractive index material of the outermost layer.

(25) Examples 1 to 8 may satisfy the following inequality (2):

$$0.2 \leq n_{\text{sub.1}} d_{\text{sub.1}} / (n_{\text{sub.1}} d_{\text{sub.1}} + n_{\text{sub.2}} d_{\text{sub.2}}) \leq 0.9 \quad (2)$$

(26) Inequality (2) may be replaced with inequality (2a) below:

$$0.6 \leq n_{\text{sub.1}} d_{\text{sub.1}} / (n_{\text{sub.1}} d_{\text{sub.1}} + n_{\text{sub.2}} d_{\text{sub.2}}) \leq 0.9 \quad (2a)$$

(27) If the film thickness of the layer 01 of the multilayer film **101** becomes larger, an average refractive index of the multilayer film **101** becomes lowered but it becomes difficult to secure the adhesion due to the increase in tensile stress. On the other hand, if the film thickness of the layer 02 becomes larger, the tensile stress is reduced and it becomes easier to secure adhesion, but the average refractive index of the multilayer film **101** increases. Maintaining the film thickness of each film satisfying inequality (2) can achieve both the antireflection performance and the adhesion.

(28) The substrate **200** made of a resin material may be deformed or cracked due to heating. Thus, the antireflection film **100** needs to be formed without heating (or with low-temperature heating of 80° C. or less). Magnesium fluoride vapor-deposited without heating (or by heating at a low temperature of 80° C. or less) has a low film strength. A resin material generally has a larger coefficient of thermal expansion than that of glass. Since the substrate **200** itself easily expands, forming a film with a large compressive stress on the substrate **200** can easily prevent film cracking and film peeling. From the above two points, the magnesium fluoride layer may be sandwiched between layers containing a silicon oxide material containing a small amount of aluminum.

(29) Examples 1 to 8 may satisfy the following inequality (3):

$$1.4 \leq n_{\text{sub.2}} \leq 1.5 \quad (3)$$

(30) In Examples 1 to 8, the layer 02 may include silicon oxide at a weight ratio of 90% or more. The layer 02 may contain aluminum oxide at a weight ratio of 10% or less. Even a silicon oxide film containing aluminum oxide at a weight ratio of 0.001% can prevent film cracking and film peeling when combined with a magnesium fluoride film. Since the multilayer film **101** is a layer equivalent to the outermost low-refractive-index material layer, the antireflection performance deteriorates if the refractive index becomes 1.5 or higher.

(31) Referring now to FIG. 2, a description will be given of a schematic structure of an optical element **301** according to each of Examples 9 to 12. FIG. 2 is a schematic sectional view of the optical element **301**. The optical element **301** includes a substrate (base material) **200** and an antireflection film **110** formed on the substrate **200**. The antireflection film **110** includes a multilayer film (first film) **111** and a multilayer film (second film) **101** in order from the substrate **200**. That is, the antireflection film **100** includes the multilayer film **111** formed on the substrate **200** and the multilayer film **101** formed on the multilayer film **111** (formed farthest from the substrate **200**).

(32) The multilayer film **101** includes, in order from the side closer to the multilayer film **111**, layer (first layer) 02-1, layer (second layer) 01, layer (third layer) 02-2, and layer (fourth layer) 03. The layer 02-1 includes silicon oxide and a small amount of aluminum (aluminum oxide). The layer 01 includes magnesium fluoride. The layer 02-2 includes silicon oxide and a small amount of aluminum (aluminum oxide). The layer 03 includes a fluorine-containing organic compound.

(33) Examples 9 to 12 may satisfy the following inequality (4):

$$\lambda/8 \leq n_{\text{sub.2-1}} d_{\text{sub.2-1}} + n_{\text{sub.1}} d_{\text{sub.1}} + n_{\text{sub.2-2}} d_{\text{sub.2-2}} + n_{\text{sub.3}} d_{\text{sub.3}} \leq \lambda/2 \quad (4)$$

where $n_{\text{sub.2-1}}$, $n_{\text{sub.1}}$, $n_{\text{sub.2-2}}$, and $n_{\text{sub.3}}$ are refractive indices for the d-line of the layers 02-1, 01, 02-2, and 03, $d_{\text{sub.2-1}}$, $d_{\text{sub.1}}$, $d_{\text{sub.2-2}}$, and $d_{\text{sub.3}}$ (nm) are physical film thicknesses of the layers 02-1, 01, 02-2, and 03, respectively, and λ is the wavelength of the d-line.

(34) Inequality (4) may be replaced with inequality (4a) below:

$$\lambda/6 \leq n_{\text{sub.2-1}} + n_{\text{sub.1d.sub.1}} + n_{\text{sub.2-2}} + n_{\text{sub.3d.sub.3}} \leq \lambda/3 \quad (4a)$$

(35) This example may satisfy the following inequalities (5) and (6):

$$0.2 \leq n_{\text{sub.1d.sub.1}} / (n_{\text{sub.2-1}} + n_{\text{sub.1d.sub.1}} + n_{\text{sub.2-2}}) \leq 0.9 \quad (5)$$

$$0.5 \leq n_{\text{sub.2-1}} / n_{\text{sub.2-2}} \leq 2.0 \quad (6)$$

(36) Inequalities (5) and (6) may be replaced with the following inequalities (5a) and (6a):

$$0.4 \leq n_{\text{sub.1d.sub.1}} / (n_{\text{sub.2-1}} + n_{\text{sub.1d.sub.1}} + n_{\text{sub.2-2}}) \leq 0.8 \quad (5a)$$

$$0.8 \leq n_{\text{sub.2-1}} / n_{\text{sub.2-2}} \leq 1.2 \quad (6a)$$

(37) Examples 9 to 12 can improve the strength by sandwiching the layer 01 containing magnesium fluoride between the layers 02-1 and 02-2 containing silicon oxide and a small amount of aluminum (aluminum oxide). The stress of the substrate **200** can be canceled by applying compressive stress to the antireflection film **110**.

(38) Examples 9 to 12 may satisfy the following inequalities (7) and (8):

$$1.4 \leq n_{\text{sub.2-1}} \leq 1.5 \quad (7)$$

$$1.4 \leq n_{\text{sub.2-2}} \leq 1.5 \quad (8)$$

(39) In Examples 9 to 12, each of the layers 02-1 and 02-2 may include silicon oxide at a weight ratio of 90% or more. Each of the layers 02-1 and 02-2 may include aluminum oxide at a weight ratio of 10% or less. Addition of aluminum is effective even if it is a very small amount. A silicon oxide film containing aluminum oxide even at a weight ratio of 0.001% can prevent film cracking and film peeling when combined with a magnesium fluoride film. Since the multilayer film **101** is a layer equivalent to the outermost low-refractive-index material layer, the antireflection performance deteriorates if the refractive index becomes 1.5 or higher.

(40) In the optical elements **300** and **301**, the film thickness $d_{\text{sub.3}}$ of the layer 03 made of the fluorine-containing organic compound may satisfy the following inequality (9):

$$2 \leq d_{\text{sub.3}} \leq 10 \quad (9)$$

(41) This is because if the film thickness is thin, the water repellency and antifouling effects are reduced, and the surface becomes cloudy, impairing its function.

(42) In the optical elements **300** and **301**, the material for the layer 03 may use a halogenated silane compound such as dimethyldichlorosilane, diethyldichlorosilane, or diphenylvinylchlorosilane, or an alkoxysilane compound such as dimethyldiethoxysilane. The material for the layer 03 may use an aminosilane compound such as bis(dimethylamino)methylsilane, hexamethyldisilazane, or a fluorine-containing aminosilane compound. These fluorine-containing organic compounds are not particularly limited as long as they can impart functions such as water repellency, oil repellency and dust resistance.

(43) The multilayer film **111** may be made of a combination of a high refractive index material and a medium refractive index material (having a refractive index of about 1.6 to 1.8 for the d-line), or layers (alternating layers) made by alternately laminating the high refractive index material and the low refractive index material. In a case where the substrate **200** is made of a resin material, the layers may be alternating layers of a high refractive index material and a low refractive index material. Since the resin material is likely to thermally expand, the low refractive index material may be the same material as that of the layer 02 having a large compressive stress. On the other hand, in a case where the substrate **200** is made of a glass material, the layer 11 of the multilayer film **111** may be made of a material containing aluminum oxide as the main component from the viewpoint of preventing white stains. The high refractive index material may be one of tantalum oxide, titanium oxide, lanthanum oxide, and zirconia oxide, or a material whose main component is a mixture of a plurality of them.

(44) The film formation method of the antireflection film **100** (or the antireflection film **110**) including the multilayer film **111** and the multilayer film **101** is not particularly limited as long as it is a physical vapor deposition method such as a vapor deposition method, a sputtering method, or an ion plating method. In particular, the vapor deposition method may be used because fluoride is less likely to decompose. In the vapor deposition method, methods for heating the vapor deposition

material include a resistance heating method, an electron beam evaporation vapor deposition method, a laser vapor deposition method, and the like. The electron beam evaporation method may be used because it can directly heat the film material, so that the film can be formed on the substrate **200** in an unheated state, the contamination is small, and the film has relatively high quality. An ion beam assist method may also be used. An independent ion source plays a role of assisting vapor deposition, so that a dense and strong film with little absorption or scattering can be formed.

(45) Each example will be specifically described below.

Example 1

(46) FIG. **1** is a schematic sectional view of the optical element **300** according to Example 1. The optical element **300** according to this example is an optical element in which the antireflection film **100** is formed on the substrate **200**. The substrate **200** is made of S-BSL7 (manufactured by OHARA) having a refractive index of 1.52 for the d-line. SiO.sub.2 (Al at a weight ratio of 4.5%), MgF.sub.2, Ta.sub.2O.sub.5, and Al.sub.2O.sub.3 are used as the layer materials. OF-SR (manufactured by Canon Optron) is used as the fluorine-containing organic compound. Table 1 illustrates the details of the film structure of the optical element according to this example. The refractive index and film thickness of each material satisfy inequalities (1), (2), (3), and (9).

(47) The film formation method of the antireflection film **100** according to this example is as follows: The antireflection film **100** is formed by vapor deposition. The inside of the vacuum chamber of the vapor deposition apparatus is evacuated to a high vacuum region of around 2×10^{-3} (Pa). The film formation temperature for each layer of the multilayer film **111** and the layers 01 and 02 of the multilayer film **101** is set to 200° C. and electron beam evaporation is used. In order to form a denser film, the ion beam assisted vapor deposition method is used. After it is confirmed that the inside of the vacuum chamber has reached a high vacuum state, Ar as an inert gas is introduced into the ion gun to discharge the ion gun. After the ion gun reaches a stable state, oxygen is introduced into the vacuum chamber, and ion-assisted vapor deposition is performed using oxygen ions at a vacuum pressure of about 1×10^{-2} (Pa). For the layer 03 of multilayer film **101**, the film formation temperature is set to 80° C. and the resistive heating deposition method is used. After the film formation is completed, excess OF-SR is removed by wiping the surface of the ejected optical element **300** with ethanol.

(48) FIG. **3** illustrates a reflectance characteristic of the optical element according to this example. In FIG. **3**, a horizontal axis represents wavelength (nm) and a vertical axis represents reflectance (%). The reflectance is maintained to be 0.3% or less in the wavelength range of 420 to 680 nm, and an excellent characteristic is demonstrated.

(49) The layer 01 made of magnesium fluoride has a strong tensile stress. On the other hand, the layer 02 made of silicon oxide containing aluminum at a weight ratio of 4.5% has strength and compressive stress. Placing the layer 02 having a strong compressive stress on top of the layer 01 having a strong tensile stress can cancel these stresses. Thereby, the antireflection film **100** is a film excellent in environmental reliability and less likely to cause cracks and peeling.

(50) In order to confirm the durability of the antireflection film **100** under various conditions, the following durability tests are conducted.

(51) (High-Temperature and High-Humidity Exposure Test (H-Temp & H-Humid in Table 13))

(52) After the prepared sample is exposed in a constant temperature bath set at a temperature of 60° C. and a humidity of 90% for 1000 hours, the appearance of the antireflection film **100** is visually observed.

(53) (Low-Temperature Exposure Test (Low-Temp Test in Table 13))

(54) After the prepared sample is exposed in a constant temperature bath set at -30° C. for 1000 hours, the appearance of the antireflection film **100** is visually observed.

(55) (High-Temperature Exposure Test (High-Temp Test in Table 13))

(56) After the prepared sample is exposed in a constant temperature bath set at 70° C. for 12 hours, the appearance of the antireflection film **100** is visually observed.

(57) (Adhesion Test)

(58) After an adhesive tape is attached to the surface of the antireflection film **100** of the prepared sample, the tape is peeled off in a direction perpendicular to the film surface. This operation is repeated 5 times, and it is visually observed whether or not the film is peeled off.

(59) (Surface Hardness Test)

(60) The antireflection film **100** is rubbed back and forth 10 times with a load of about 200 g on a silicon paper soaked with a solvent, and then the appearance of the antireflection film **100** is visually observed.

(61) Table 13 illustrates the results of the durability tests. In any test, it can be confirmed that an excellent antireflection film is formed without film cracking or film peeling.

(62) TABLE-US-00001 TABLE 1 Physical Refractive Film Index Thickness (d-line) (nm)

Multilayer Layer 03 Fluorine-containing 1.35 3.0 Film 101 Organic Compound Layer 02 SiO₂.sub.2 (Al-containing: 1.47 20.0 weight ratio of 4.5%) Layer 01 MgF₂.sub.2 1.39 69.2 Multilayer Layer 16 Ta₂O₅.sub.5 2.11 38.0 Film 111 Layer 15 Al₂O₃.sub.3 1.63 12.0 Layer 14 Ta₂O₅.sub.5 2.11 56.2 Layer 13 Al₂O₃.sub.3 1.63 16.8 Layer 12 Ta₂O₅.sub.5 2.11 12.0 Layer 11 Al₂O₃.sub.3 1.63 70.2 Substrate S-BSL7 1.52 — 200

Example 2

(63) In the optical element **300** according to Example 2, the substrate **200** is made of S-BSM14 (manufactured by OHARA) having a refractive index of 1.60 for the d-line. The optical element **300** according to this example is manufactured using the same vapor deposition material and under the same vapor deposition condition as those of Example 1. Table 2 illustrates the details of the film structure of the optical element according to this example. The refractive index and film thickness of each material satisfy inequalities (1), (2), (3), and (9). FIG. 4 illustrates a reflectance characteristic of the optical element according to this example. In FIG. 4, a horizontal axis represents wavelength (nm) and a vertical axis represents reflectance (%). The reflectance is maintained to be 0.25% or less in the wavelength range of 420 to 680 nm, and an excellent characteristic is demonstrated.

(64) Table 13 illustrates the results of the durability tests. In any test, it can be confirmed that an excellent antireflection film is formed without film cracking or film peeling.

(65) TABLE-US-00002 TABLE 2 Physical Refractive Film Index Thickness (d-line) (nm)

Multilayer Layer 03 Fluorine-containing 1.35 3.0 Film 101 Organic Compound Layer 02 SiO₂.sub.2 (Al-containing: 1.47 25.0 weight ratio of 4.5%) Layer 01 MgF₂.sub.2 1.39 65.9 Multilayer Layer 16 Ta₂O₅.sub.5 2.11 47.0 Film 111 Layer 15 Al₂O₃.sub.3 1.63 12.0 Layer 14 Ta₂O₅.sub.5 2.11 62.8 Layer 13 Al₂O₃.sub.3 1.63 42.2 Layer 12 Ta₂O₅.sub.5 2.11 12.0 Layer 11 Al₂O₃.sub.3 1.63 157.7 Substrate S-BSM14 1.60 — 200

Example 3

(66) In the optical element **300** according to Example 3, the substrate **200** is made of S-BAH32 (manufactured by OHARA) having a refractive index of 1.67 for the d-line. SiO₂.sub.2, Ta₂O₅.sub.5, and MgF₂.sub.2 containing Al at a weight ratio of 4.5% are used as layer materials. OF-SR (manufactured by Canon Optron) is used as the fluorine-containing organic compound. The optical element **300** according to this example is manufactured under the same vapor deposition condition as that of Example 1. Table 3 illustrates the details of the film structure of the optical element according to this example. The refractive index and film thickness of each material satisfy inequalities (1), (2), (3), and (9). FIG. 5 illustrates a reflectance characteristic of the optical element according to this example. In FIG. 5, a horizontal axis represents wavelength (nm) and a vertical axis represents reflectance (%). The reflectance is maintained to be 0.25% or less in the wavelength range of 420 to 680 nm, and an excellent characteristic is demonstrated.

(67) Table 13 illustrates the results of the durability tests. In any test, it can be confirmed that an excellent antireflection film is formed without film cracking or film peeling.

(68) TABLE-US-00003 TABLE 3 Physical Refractive Film Index Thickness (d-line) (nm)

Multilayer Layer 03 Fluorine-containing 1.35 3.0 Film 101 Organic Compound Layer 02 SiO.sub.2 (Al-containing: 1.47 24.0 weight ratio of 4.5%) Layer 01 MgF.sub.2 1.39 67.3 Multilayer Layer 16 Ta.sub.2O.sub.5 2.11 56.0 Film 111 Layer 15 SiO.sub.2 (Al-containing: 1.47 12.0 weight ratio of 4.5%) Layer 14 Ta.sub.2O.sub.5 2.11 56.2 Layer 13 SiO.sub.2 (Al-containing: 1.47 48.9 weight ratio of 4.5%) Layer 12 Ta.sub.2O.sub.5 2.11 19.0 Layer 11 SiO.sub.2 (Al-containing: 1.47 44.6 weight ratio of 4.5%) Substrate S-BAH32 1.67 — 200

Example 4

(69) In the optical element **300** according to Example 4, the substrate **200** is made of S-LAH66 (manufactured by OHARA) having a refractive index of 1.77 for the d-line. The optical element **300** according to this example is manufactured using the same vapor deposition material as that of Example 3 and under the same vapor deposition condition as that of Example 1. Table 4 illustrates the details of the film structure of the optical element according to this example. The refractive index and film thickness of each material satisfy inequalities (1), (2), (3), and (9). FIG. 6 illustrates a reflectance characteristic of the optical element according to this example. In FIG. 6, a horizontal axis represents wavelength (nm) and a vertical axis represents reflectance (%). The reflectance is maintained to be 0.2% or less in the wavelength range of 420 to 680 nm, and an excellent characteristic is demonstrated.

(70) Table 13 illustrates the results of the durability tests. In any test, it can be confirmed that an excellent antireflection film is formed without film cracking or film peeling.

(71) TABLE-US-00004 TABLE 4 Physical Refractive Film Index Thickness (d-line) (nm)

Multilayer Layer 03 Fluorine-containing 1.35 3.0 Film 101 Organic Compound Layer 02 SiO.sub.2 (Al-containing: 1.47 15.0 weight ratio of 4.5%) Layer 01 MgF.sub.2 1.39 78.4 Multilayer Layer 16 Ta.sub.2O.sub.5 2.11 52.7 Film 111 Layer 15 SiO.sub.2 (Al-containing: 1.47 12.0 weight ratio of 4.5%) Layer 14 Ta.sub.2O.sub.5 2.11 61.4 Layer 13 SiO.sub.2 (Al-containing: 1.47 41.1 weight ratio of 4.5%) Layer 12 Ta.sub.2O.sub.5 2.11 25.4 Layer 11 SiO.sub.2 (Al-containing: 1.47 33.1 weight ratio of 4.5%) Substrate S-LAH66 1.77 — 200

Example 5

(72) In the optical element **300** according to Example 5, the substrate **200** is made of S-TIH53 (manufactured by OHARA) having a refractive index of 1.85 for the d-line. The optical element **300** according to this example is manufactured using the same vapor deposition material as that of Example 4 and under the same vapor deposition condition as that of Example 1. Table 5 illustrates the details of the film structure of the optical element according to this example. The refractive index and film thickness of each material satisfy inequalities (1), (2), (3), and (9). FIG. 7 illustrates a reflectance characteristic of the optical element according to this example. In FIG. 7, a horizontal axis represents wavelength (nm) and a vertical axis represents reflectance (%). The reflectance is maintained to be 0.3% or less in the wavelength range of 420 to 720 nm, and an excellent characteristic is demonstrated.

(73) Table 13 illustrates the results of the durability tests. In any test, it can be confirmed that an excellent antireflection film is formed without film cracking or film peeling.

(74) TABLE-US-00005 TABLE 5 Physical Refractive Film Index Thickness (d-line) (nm)

Multilayer Layer 03 Fluorine-containing 1.35 3.0 Film 101 Organic Compound Layer 02 SiO.sub.2 (Al-containing: 1.47 30.0 weight ratio of 4.5%) Layer 01 MgF.sub.2 1.39 63.8 Multilayer Layer 16 Ta.sub.2O.sub.5 2.11 50.7 Film 111 Layer 15 SiO.sub.2 (Al-containing: 1.47 12.0 weight ratio of 4.5%) Layer 14 Ta.sub.2O.sub.5 2.11 68.5 Layer 13 SiO.sub.2 (Al-containing: 1.47 34.7 weight ratio of 4.5%) Layer 12 Ta.sub.2O.sub.5 2.11 31.5 Layer 11 SiO.sub.2 (Al-containing: 1.47 27.5 weight ratio of 4.5%) Substrate S-TIH53 1.85 — 200

Example 6

(75) In the optical element **300** according to Example 6, the substrate **200** is made of S-NPH3 (manufactured by OHARA) having a refractive index of 1.96 for the d-line. The optical element **300** according to this example is manufactured using the same deposition material as that of

Example 4 and under the same deposition condition as that of Example 1. Table 6 illustrates the details of the film structure of the optical element according to this example. The refractive index and film thickness of each material satisfy inequalities (1), (2), (3), and (9). FIG. 8 illustrates a reflectance characteristic of the optical element according to this example. In FIG. 8, a horizontal axis represents wavelength (nm) and a vertical axis represents reflectance (%). The reflectance is maintained to be 0.4% or less in the wavelength range of 420 to 720 nm, and an excellent characteristic is demonstrated.

(76) Table 13 illustrates the results of the durability tests. In any test, it can be confirmed that an excellent antireflection film is formed without film cracking or film peeling.

(77) TABLE-US-00006 TABLE 6 Physical Refractive Film Index Thickness (d-line) (nm)

Multilayer Layer 03 Fluorine-containing 1.35 3.0 Film 101 Organic Compound Layer 02 SiO.sub.2 (Al-containing: 1.47 35.0 weight ratio of 4.5%) Layer 01 MgF.sub.2 1.39 58.4 Multilayer Layer 16 Ta.sub.2O.sub.5 2.11 51.7 Film 111 Layer 15 SiO.sub.2 (Al-containing: 1.47 12.0 weight ratio of 4.5%) Layer 14 Ta.sub.2O.sub.5 2.11 69.2 Layer 13 SiO.sub.2 (Al-containing: 1.47 32.3 weight ratio of 4.5%) Layer 12 Ta.sub.2O.sub.5 2.11 37.0 Layer 11 SiO.sub.2 (Al-containing: 1.47 23.7 weight ratio of 4.5%) Substrate S-NPH3 1.96 — 200

Example 7

(78) In the optical element **300** according to Example 7, the substrate **200** is made of S-LAH79 (manufactured by OHARA) having a refractive index of 2.00 for the d-line. The optical element **300** according to this example is manufactured using the same deposition material as that of Example 4 and under the same deposition condition as that of Example 1. Table 7 illustrates the details of the film structure of the optical element according to this example. The refractive index and film thickness of each material satisfy inequalities (1), (2), (3), and (9). FIG. 9 illustrates a reflectance characteristic of the optical element according to this example. In FIG. 9, a horizontal axis represents wavelength (nm) and a vertical axis represents reflectance (%). The reflectance is maintained to be 0.3% or less in the wavelength range of 420 to 720 nm, and an excellent characteristic is demonstrated.

(79) Table 13 illustrates the results of the durability tests. In any test, it can be confirmed that an excellent antireflection film is formed without film cracking or film peeling.

(80) TABLE-US-00007 TABLE 7 Physical Refractive Film Index Thickness (d-line) (nm)

Multilayer Layer 03 Fluorine-containing 1.35 3.0 Film 101 Organic Compound Layer 02 SiO.sub.2 (Al-containing: 1.47 15.0 weight ratio of 4.5%) Layer 01 MgF.sub.2 1.39 81.8 Multilayer Layer 16 Ta.sub.2O.sub.5 2.11 44.7 Film 111 Layer 15 SiO.sub.2 (Al-containing: 1.47 12.0 weight ratio of 4.5%) Layer 14 Ta.sub.2O.sub.5 2.11 78.3 Layer 13 SiO.sub.2 (Al-containing: 1.47 24.5 weight ratio of 4.5%) Layer 12 Ta.sub.2O.sub.5 2.11 41.6 Layer 11 SiO.sub.2 (Al-containing: 1.47 18.5 weight ratio of 4.5%) Substrate S-LAH79 2.00 — 200

Example 8

(81) In the optical element **300** according to Example 8, the substrate **200** is made of fluorite having a refractive index of 1.43 for the d-line. The layer materials use SiO.sub.2 containing Al at a weight ratio of 4.5%, a mixture of Ti.sub.2O.sub.3 and Ta.sub.2O.sub.5, and MgF.sub.2. OF-SR (manufactured by Canon Optron) is used as the fluorine-containing organic compound. Fluorite cracks when it is cooled rapidly. Therefore, the antireflection film **100** is vapor-deposited without heating. The optical element **300** according to this example is manufactured under the same vacuum and ion assist conditions as those of Example 1. SiO.sub.2 containing Al at a weight ratio of 4.5%, a mixture of Ti.sub.2O.sub.3 and Ta.sub.2O.sub.5, and MgF.sub.2 are subjected to ion-assisted deposition to increase strength. Table 8 illustrates the details of the film structure of the optical element according to this example. The refractive index and film thickness of each material satisfy inequalities (1), (2), (3), and (9). FIG. 10 illustrates a reflectance characteristic of the optical element according to this example. In FIG. 10, a horizontal axis represents wavelength (nm) and a vertical axis represents reflectance (%). The reflectance is maintained to be 0.2% or less in the

wavelength range of 420 to 680 nm, and an excellent characteristic is demonstrated.

(82) Table 13 illustrates the results of the durability tests. In any test, it can be confirmed that an excellent antireflection film is formed without film cracking or film peeling.

(83) TABLE-US-00008 TABLE 8 Physical Refractive Film Index Thickness (d-line) (nm)

Multilayer Layer 03 Fluorine-containing 1.35 3.0 Film 101 Organic Compound Layer 02 SiO.sub.2 (Al-containing: 1.47 15.0 weight ratio of 4.5%) Layer 01 MgF.sub.2 1.39 81.8 Multilayer Layer 16 Ti.sub.2O.sub.3 + Ta.sub.2O.sub.5 2.11 44.7 Film 111 Layer 15 SiO.sub.2 (Al-containing: 1.47 12.0 weight ratio of 4.5%) Layer 14 Ti.sub.2O.sub.3 + Ta.sub.2O.sub.5 2.11 78.3 Layer 13 SiO.sub.2 (Al-containing: 1.47 24.5 weight ratio of 4.5%) Layer 12 Ti.sub.2O.sub.3 + Ta.sub.2O.sub.5 2.11 41.6 Layer 11 SiO.sub.2 (Al-containing: 1.47 18.5 weight ratio of 4.5%) Substrate CaF.sub.2 1.43 — 200

Example 9

(84) The optical element **300** according to Example 9 is an optical element in which the antireflection film **110** is formed on the substrate **200**. The substrate **200** is made of E48R (manufactured by Nippon Zeon Co., Ltd.) having a refractive index of 1.53 for the d-line. The layer materials use SiO.sub.2 containing Al at a weight ratio of 4.5%, a mixture of Ti.sub.2O.sub.3 and Ta.sub.2O.sub.5, and MgF.sub.2. OF-SR (manufactured by Canon Optron) is used as the fluorine-containing organic compound. E48R (substrate **200**), which is a resin material, is deformed at a high temperature. Therefore, the antireflection film **100** is vapor-deposited without heating. The optical element **300** according to this example is manufactured under the same vacuum and ion assist conditions as those of Example 1. SiO.sub.2 containing Al at a weight ratio of 4.5%, a mixture of Ti.sub.2O.sub.3 and Ta.sub.2O.sub.5, and MgF.sub.2 are subjected to ion-assisted deposition to increase strength. Table 9 illustrates the details of the film structure of the optical element according to this example. The refractive index and film thickness of each material satisfy inequalities (4), (5), (6), (7), (8), and (9). FIG. **11** illustrates a reflectance characteristic of the optical element according to this example. In FIG. **11**, a horizontal axis represents wavelength (nm) and a vertical axis represents reflectance (%). The reflectance is maintained to be 0.2% or less in the wavelength range of 420 to 680 nm, and an excellent characteristic is demonstrated.

(85) Table 13 illustrates the results of the durability tests. In any test, it can be confirmed that an excellent antireflection film is formed without film cracking or film peeling.

(86) TABLE-US-00009 TABLE 9 Physical Refractive Film Index Thickness (d-line) (nm)

Multilayer Layer 04 Fluorine-containing 1.35 3.0 Film 101 Organic Compound Layer 03 SiO.sub.2 (Al-containing: 1.47 20.0 weight ratio of 4.5%) Layer 02 MgF.sub.2 1.39 52.8 Layer 01 SiO.sub.2 (Al-containing: 1.47 20.0 weight ratio of 4.5%) Multilayer Layer 16 Ti.sub.2O.sub.3 + Ta.sub.2O.sub.5 2.11 54.8 Film 111 Layer 15 SiO.sub.2 (Al-containing: 1.47 12.0 weight ratio of 4.5%) Layer 14 Ti.sub.2O.sub.3 + Ta.sub.2O.sub.5 2.11 52.0 Layer 13 SiO.sub.2 (Al-containing: 1.47 50.5 weight ratio of 4.5%) Layer 12 Ti.sub.2O.sub.3 + Ta.sub.2O.sub.5 2.11 12.0 Layer 11 SiO.sub.2 (Al-containing: 1.47 75.4 weight ratio of 4.5%) Substrate E48R 1.53 — 200

Example 10

(87) In the optical element **301** according to Example 10, the substrate **200** is made of EP-5000 (manufactured by Mitsui Gas Chemicals) having a refractive index of 1.64 for the d-line. The optical element **301** according to this example is manufactured using the same vapor deposition material and under the same vapor deposition condition as those of Example 9. Table 10 illustrates the details of the film structure of the optical element according to this example. The refractive index and film thickness of each material satisfy inequalities (4), (5), (6), (7), (8), and (9). FIG. **12** illustrates a reflectance characteristic of the optical element according to this example. In FIG. **12**, a horizontal axis represents wavelength (nm) and a vertical axis represents reflectance (%). The reflectance is maintained to be 0.2% or less in the wavelength range of 420 to 680 nm, and an excellent characteristic is demonstrated.

(88) Table 13 illustrates the results of the durability tests. In any test, it can be confirmed that an

excellent antireflection film is formed without film cracking or film peeling.

(89) TABLE-US-00010 TABLE 10 Physical Refractive Film Index Thickness (d-line) (nm)
Multilayer Layer 04 Fluorine-containing 1.35 3.0 Film 101 Organic Compound Layer 03 SiO.sub.2
(Al-containing: 1.47 25.0 weight ratio of 4.5%) Layer 02 MgF.sub.2 1.39 46.6 Layer 01 SiO.sub.2
(Al-containing: 1.47 20.0 weight ratio of 4.5%) Multilayer Layer 16 Ti.sub.2O.sub.3 +
Ta.sub.2O.sub.5 2.11 59.9 Film 111 Layer 15 SiO.sub.2 (Al-containing: 1.47 12.0 weight ratio of
4.5%) Layer 14 Ti.sub.2O.sub.3 + Ta.sub.2O.sub.5 2.11 49.7 Layer 13 SiO.sub.2 (Al-containing:
1.47 56.8 weight ratio of 4.5%) Layer 12 Ti.sub.2O.sub.3 + Ta.sub.2O.sub.5 2.11 14.5 Layer 11
SiO.sub.2 (Al-containing: 1.47 57.4 weight ratio of 4.5%) Substrate EP-5000 1.64 — 200

Example 11

(90) In the optical element **301** according to Example 11, the substrate **200** is made of E48R (manufactured by Nippon Zeon Co., Ltd.) having a refractive index of 1.53 for the d-line. The optical element **301** according to this example is manufactured using the same vapor deposition material and under the same vapor deposition conditions as those of Example 11. Table 11 illustrates the details of the film structure of the optical element according to this example. The refractive index and film thickness of each material satisfy inequalities (4), (5), (6), (7), (8), and (9). FIG. 13 illustrates a reflectance characteristic of the optical element according to this example. In FIG. 13, a horizontal axis represents wavelength (nm) and a vertical axis represents reflectance (%). The reflectance is maintained to be 0.4% or less in the wavelength range of 420 to 760 nm, and an excellent characteristic is demonstrated.

(91) Table 13 illustrates the results of the durability tests. In any test, it can be confirmed that an excellent antireflection film is formed without film cracking or film peeling.

(92) TABLE-US-00011 TABLE 11 Physical Refractive Film Index Thickness (d-line) (nm)
Multilayer Layer 04 Fluorine-containing 1.35 3.0 Film 101 Organic Compound Layer 03 SiO.sub.2
(Al-containing: 1.47 25.0 weight ratio of 4.5%) Layer 02 MgF.sub.2 1.39 53.1 Layer 01 SiO.sub.2
(Al-containing: 1.47 20.0 weight ratio of 4.5%) Multilayer Layer 16 Ti.sub.2O.sub.3 +
Ta.sub.2O.sub.5 2.11 46.4 Film 111 Layer 15 SiO.sub.2 (Al-containing: 1.47 12.0 weight ratio of
4.5%) Layer 14 Ti.sub.2O.sub.3 + Ta.sub.2O.sub.5 2.11 68.0 Layer 13 SiO.sub.2 (Al-containing:
1.47 38.7 weight ratio of 4.5%) Layer 12 Ti.sub.2O.sub.3 + Ta.sub.2O.sub.5 2.11 18.9 Layer 11
SiO.sub.2 (Al-containing: 1.47 38.6 weight ratio of 4.5%) Substrate E48R 1.53 — 200

Example 12

(93) In the optical element **301** according to Example 12, the substrate **200** is made of EP-5000 (Mitsubishi Gas Chemical Co., Ltd.) having a refractive index of 1.64 for the d-line. The optical element **301** according to this example is manufactured using the same vapor deposition material and under the same vapor deposition condition as those of Example 9. Table 12 illustrates the details of the film structure of the optical element according to this example. The refractive index and film thickness of each material satisfy inequalities (4), (5), (6), (7), (8), and (9). FIG. 14 illustrates a reflectance characteristic of the optical element according to this example. In FIG. 14, a horizontal axis represents wavelength (nm) and a vertical axis represents reflectance (%). The reflectance is maintained to be 0.4% or less in the wavelength range of 420 to 760 nm, and an excellent characteristic is demonstrated.

(94) Table 13 illustrates the results of the durability tests. In any test, it can be confirmed that an excellent antireflection film is formed without film cracking or film peeling.

(95) TABLE-US-00012 TABLE 12 Physical Refractive Film Index Thickness (d-line) (nm)
Multilayer Layer 04 Fluorine-containing 1.35 3.0 Film 101 Organic Compound Layer 03 SiO.sub.2
(Al-containing: 1.47 20.0 weight ratio of 4.5%) Layer 02 MgF.sub.2 1.39 59.4 Layer 01 SiO.sub.2
(Al-containing: 1.47 20.0 weight ratio of 4.5%) Multilayer Layer 16 Ti.sub.2O.sub.3 +
Ta.sub.2O.sub.5 2.11 44.0 Film 111 Layer 15 SiO.sub.2 (Al-containing: 1.47 12.0 weight ratio of
4.5%) Layer 14 Ti.sub.2O.sub.3 + Ta.sub.2O.sub.5 2.11 73.4 Layer 13 SiO.sub.2 (Al-containing:
1.47 34.5 weight ratio of 4.5%) Layer 12 Ti.sub.2O.sub.3 + Ta.sub.2O.sub.5 2.11 24.3 Layer 11

SiO₂ sub.2 (Al-containing: 1.47 31.5 weight ratio of 4.5%) Substrate EP-5000 1.64 — 200
(96) TABLE-US-00013 TABLE 13 H-Temp Low- High- AR & Temp Temp Adhesion Surface
Effect H-Humid Test Test Test Hardness Example 1 ○ ○ ○ ○ ○ ○ Example 2 ○ ○ ○ ○ ○ ○ Example
3 ○ ○ ○ ○ ○ ○ Example 4 ○ ○ ○ ○ ○ ○ Example 5 ○ ○ ○ ○ ○ ○ Example 6 ○ ○ ○ ○ ○ ○ Example 7
○ ○ ○ ○ ○ ○ Example 8 ○ ○ ○ ○ ○ ○ Example 9 ○ ○ ○ ○ ○ ○ Example 10 ○ ○ ○ ○ ○ ○ Example
11 ○ ○ ○ ○ ○ ○ Example 12 ○ ○ ○ ○ ○ ○

Example 13

(97) Referring now to FIG. 15, a description will be given of an optical system according to Example 13. FIG. 15 is a sectional view of an optical system 400. The optical system 400 includes a plurality of optical elements G401 to G411. Reference numeral 402 denotes an aperture stop (diaphragm), and reference numeral 403 denotes an image plane. Reference numeral F412 denotes an optical filter disposed on the object side of the optical system 400.

(98) The optical elements G401 to G411 are lenses respectively. At least one of the incident surface and the exit surface of these lenses has the antireflection film according to any one of Examples 1 to 12. That is, the plurality of optical elements G401 to G411 include the optical element 300 on which the antireflection film 100 according to any one of Examples 1 to 8 is formed or the optical element 301 on which the antireflection film 110 according to any according to Examples 9 to 12 is formed.

(99) An R1 surface of the optical element G401 and an R2 surface of the optical element G411 are the outermost surfaces of optical system 400. The antireflection film 100 or the antireflection film 110 may be applied to the R1 surface and the R2 surface because dirt and the like are likely to adhere to them. The optical filter F412 is an optical element that is disposed closer to the object than the optical element G401 and is removable according to the intended use. Thus, the antireflection film 100 or the antireflection film 110 may be applied to an R3 surface and an R4 surface of the optical filter F412, because dirt and the like are likely to adhere to them.

(100) The optical system 400 according to this example is not limited to an imaging optical system that is used for an image pickup apparatus, which will be described below, and is applicable to optical systems for various purposes such as binoculars, projectors, and telescopes.

Example 14

(101) Referring now to FIG. 16, a description will be given of an image pickup apparatus (optical apparatus) according to Example 14. FIG. 16 is an external perspective view of the image pickup apparatus (digital camera 500).

(102) The digital camera 500 includes a camera body 502 and a lens apparatus (optical apparatus) 501 integrated with the camera body 502. However, this example is not limited, and the lens apparatus 501 may be an interchangeable lens attachable to and detachable from the camera body 502 for a single-lens reflex camera, a mirrorless camera, or the like. In this case, FIG. 16 corresponds to a state in which the lens apparatus 501 is attached to the camera body 502. The lens apparatus 501 includes the optical system 400 according to Example 13, for example. The camera body 502 includes an image sensor 503 such as a CMOS sensor or a CCD sensor. The image sensor 503 is disposed on the image plane 403 of the optical system 400.

(103) Each example can provide an optical element, an optical system, and an optical apparatus, each of which has high mechanical strength, environmental durability, and antifouling performance.

(104) While the disclosure has been described with reference to examples, it is to be understood that the disclosure is not limited to the disclosed examples. The scope of the following claims is to be accorded the broadest interpretation so as to encompass all such modifications and equivalent structures and functions.

(105) This application claims the benefit of Japanese Patent Application No. 2022-041285, filed on Mar. 16, 2022, which is hereby incorporated by reference herein in its entirety.

Claims

1. An antireflection film comprising: a first film formed on a substrate; and a second film formed on the first film, wherein the second film comprises a first layer, a second layer, and a third layer arranged consecutively in order from a side closer to the first film, wherein the first layer includes magnesium fluoride, wherein the second layer includes silicon oxide at a weight ratio of 90% or more and aluminum oxide at a weight ratio of 10% or less, and wherein the third layer includes a fluorine-containing organic compound.
2. The antireflection film according to claim 1, wherein the following inequality is satisfied: $\lambda/8 \leq n_{\text{sub.1}}d_{\text{sub.1}} + n_{\text{sub.2}}d_{\text{sub.2}} + n_{\text{sub.3}}d_{\text{sub.3}} \leq \lambda/2$ where $n_{\text{sub.1}}$ is a refractive index for d-line of the first layer, $n_{\text{sub.2}}$ is a refractive index for the d-line of the second layer, $n_{\text{sub.3}}$ is a refractive index for the d-line of the third layer, $d_{\text{sub.1}}$ (nm) is a physical film thickness of the first layer, $d_{\text{sub.2}}$ (nm) is a physical film thickness of the second layer, $d_{\text{sub.3}}$ (nm) is a physical film thickness of the third layer, and λ (nm) is a wavelength of the d-line.
3. The antireflection film according to claim 2, wherein the following inequality is satisfied: $\lambda/6 \leq n_{\text{sub.1}}d_{\text{sub.1}} + n_{\text{sub.2}}d_{\text{sub.2}} + n_{\text{sub.3}}d_{\text{sub.3}} \leq \lambda/3$.
4. The antireflection film according to claim 1, wherein the following inequality is satisfied: $0.2 \leq n_{\text{sub.1}}d_{\text{sub.1}} / (n_{\text{sub.1}}d_{\text{sub.1}} + n_{\text{sub.2}}d_{\text{sub.2}}) \leq 0.9$ where $n_{\text{sub.1}}$ is a refractive index for d-line of the first layer, $n_{\text{sub.2}}$ is a refractive index for the d-line of the second layer, $d_{\text{sub.1}}$ (nm) is a physical film thickness of the first layer, and $d_{\text{sub.2}}$ (nm) is a physical film thickness of the second layer.
5. The antireflection film according to claim 4, wherein the following inequality is satisfied: $0.6 \leq n_{\text{sub.1}}d_{\text{sub.1}} / (n_{\text{sub.1}}d_{\text{sub.1}} + n_{\text{sub.2}}d_{\text{sub.2}}) \leq 0.9$.
6. The antireflection film according to claim 1, wherein the following inequality is satisfied: $1.4 \leq n_{\text{sub.2}} \leq 1.5$ where $n_{\text{sub.2}}$ is a refractive index for the d-line of the second layer.
7. The antireflection film according to claim 1, wherein a layer adjacent to the second film in the first film includes tantalum oxide.
8. An optical element comprising the antireflection film according to claim 1 and the substrate.
9. An optical system comprising a plurality of optical elements, wherein the plurality of optical elements includes the optical element according to claim 8.
10. An optical apparatus comprising: an image sensor; and an optical element according to claim 1.
11. An antireflection film comprising: a first film formed on a substrate; and a second film formed on the first film, wherein the second film comprises a first layer, a second layer, a third layer, and a fourth layer in order from a side closer to the first film, wherein each of the first layer and third layer includes silicon oxide at a weight ratio of 90% or more and aluminum oxide at a weight ratio of 10% or less, wherein the second layer includes magnesium fluoride, and wherein the fourth layer includes a fluorine-containing organic compound.
12. The antireflection film according to claim 11, wherein the following inequality is satisfied: $\lambda/8 \leq n_{\text{sub.2-1}}d_{\text{sub.2-1}} + n_{\text{sub.1}}d_{\text{sub.1}} + n_{\text{sub.2-2}}d_{\text{sub.2-2}} + n_{\text{sub.3}}d_{\text{sub.3}} \leq \lambda/2$ where $n_{\text{sub.2-1}}$ is a refractive index for d-line of the first layer, $n_{\text{sub.1}}$ is a refractive index for the d-line of the second layer, $n_{\text{sub.2-2}}$ is a refractive index for the d-line of the third layer, $n_{\text{sub.3}}$ is a refractive index for the d-line of the fourth layer, $d_{\text{sub.2-1}}$ (nm) is a physical film thickness of the first layer, $d_{\text{sub.1}}$ (nm) is a physical film thickness of the second layer, $d_{\text{sub.2-2}}$ (nm) is a physical film thickness of the third layer, $d_{\text{sub.3}}$ (nm) is a physical film thickness of the fourth layer, and λ (nm) is a wavelength of the d-line.
13. The antireflection film according to claim 12, wherein the following inequality is satisfied: $\lambda/6 \leq n_{\text{sub.2-1}}d_{\text{sub.2-1}} + n_{\text{sub.1}}d_{\text{sub.1}} + n_{\text{sub.2-2}}d_{\text{sub.2-2}} + n_{\text{sub.3}}d_{\text{sub.3}} \leq \lambda/3$.
14. The antireflection film according to claim 11, wherein the following inequalities are satisfied: $0.2 \leq n_{\text{sub.1}}d_{\text{sub.1}} / (n_{\text{sub.2-1}}d_{\text{sub.2-1}} + n_{\text{sub.1}}d_{\text{sub.1}} + n_{\text{sub.2-2}}d_{\text{sub.2-2}}) \leq 0.9$

$0.5 \leq n_{\text{sub.2-1}} d_{\text{sub.2-1}} / n_{\text{sub.2-2}} d_{\text{sub.2-2}} \leq 2.0$ where $n_{\text{sub.2-1}}$ is a refractive index for d-line of the first layer, $n_{\text{sub.1}}$ is a refractive index for the d-line of the second layer, $n_{\text{sub.2-2}}$ is a refractive index for the d-line of the third layer, $n_{\text{sub.3}}$ is a refractive index of the fourth layer in the d-line, $d_{\text{sub.2-1}}$ (nm) is a physical film thickness of the first layer, $d_{\text{sub.1}}$ (nm) is a physical film thickness of the second layer, $d_{\text{sub.2-2}}$ (nm) is a physical film thickness of the third layer, $d_{\text{sub.3}}$ (nm) is a physical film thickness of the fourth layer, and λ (nm) is a wavelength of the d-line.

15. The antireflection film according to claim 14, wherein the following inequalities are satisfied:

$$0.4 \leq n_{\text{sub.1}} d_{\text{sub.1}} / (n_{\text{sub.2-1}} d_{\text{sub.2-1}} + n_{\text{sub.1}} d_{\text{sub.1}} + n_{\text{sub.2-2}} d_{\text{sub.2-2}}) \leq 0.8$$

$$0.8 \leq n_{\text{sub.2-1}} d_{\text{sub.2-1}} / n_{\text{sub.2-2}} d_{\text{sub.2-2}} \leq 1.2.$$

16. The antireflection film according to claim 11, wherein the following inequalities are satisfied:

$$1.4 \leq n_{\text{sub.2-1}} \leq 1.5$$

$1.4 \leq n_{\text{sub.2-2}} \leq 1.5$ where $n_{\text{sub.2-1}}$ is a refractive index for d-line of the first layer, and $n_{\text{sub.2-2}}$ is a refractive index for the d-line of the third layer.

17. The antireflection film according to claim 11, wherein a layer adjacent to the second film in the first film includes tantalum oxide.

18. An optical element comprising the antireflection film according to claim 11 and the substrate.

19. An optical system comprising a plurality of optical elements, wherein the plurality of optical elements includes the optical element according to claim 18.

20. An optical apparatus comprising: an image sensor; and an optical element according to claim 18.
