

# US Patent & Trademark Office

## Patent Public Search | Text View

---

|                      |                    |
|----------------------|--------------------|
| United States Patent | 12414424           |
| Kind Code            | B2                 |
| Date of Patent       | September 09, 2025 |
| Inventor(s)          | Kim; Seonki et al. |

---

### Monolithically integrated top-gate thin-film transistor and light-emitting diode and method of making

---

#### Abstract

Pixels and sub-pixels suitable for high-density displays are disclosed. High-density is realized by forming a top-gate thin-film transistor (TFT) directly on top of a light-emitting diode (LED), thereby reducing the real estate required. To enable the stacked structure, a planarization layer is formed such that its top surface is coplanar with the top surface of the top electrode of the LED. The source and drain of the TFT are then formed on the planarization layer and electrode such that electrical contact is made between the LED and the TFT. In some embodiments, the fabrication includes deposition of an additional planarization layer whose top surface is coplanar with the top surface of the gate of the TFT. This enables formation of a parallel-plate capacitor on the TFT/LED stack, thereby reducing the footprint of the pixel even further.

---

**Inventors:** Kim; Seonki (Fishkill, NY), Ghosh; Amalkumar P. (Hopewell Junction, NY)

**Applicant:** eMagin Corporation (Hopewell Junction, NY)

**Family ID:** 84542595

**Assignee:** eMagin Corporation (Hopewell Junction, NY)

**Appl. No.:** 17/850301

**Filed:** June 27, 2022

#### Prior Publication Data

| Document Identifier | Publication Date |
|---------------------|------------------|
| US 20220415966 A1   | Dec. 29, 2022    |

#### Related U.S. Application Data

us-provisional-application US 63215776 20210628

---

Publication Classification

Int. Cl.: H10H29/14 (20250101)

U.S. Cl.:

CPC H10H29/142 (20250101);

Field of Classification Search

CPC: H10H (29/142)

References Cited

U.S. PATENT DOCUMENTS

| Patent No.   | Issued Date | Patentee Name | U.S. Cl. | CPC             |
|--------------|-------------|---------------|----------|-----------------|
| 11139339     | 12/2020     | Long          | N/A      | H10D<br>30/6745 |
| 11296170     | 12/2021     | Choi          | N/A      | H10K 59/122     |
| 2015/0214249 | 12/2014     | Cheng et al.  | N/A      | N/A             |
| 2016/0126293 | 12/2015     | Li            | 257/29   | H10H 20/812     |
| 2016/0293586 | 12/2015     | Ghosh         | N/A      | H01L 25/167     |
| 2019/0355799 | 12/2018     | Jeong et al.  | N/A      | N/A             |
| 2021/0343905 | 12/2020     | Kishimoto     | N/A      | H10H<br>20/8312 |

FOREIGN PATENT DOCUMENTS

| Patent No.      | Application Date | Country | CPC |
|-----------------|------------------|---------|-----|
| 2018-060184     | 12/2017          | JP      | N/A |
| 2018-077361     | 12/2017          | JP      | N/A |
| 10-2018-0015144 | 12/2017          | KR      | N/A |
| 2018-0052977    | 12/2017          | KR      | N/A |
| 10-2019-0037568 | 12/2018          | KR      | N/A |
| 2016/179092     | 12/2015          | WO      | N/A |
| 2019/220246     | 12/2020          | WO      | N/A |
| 2020/100290     | 12/2020          | WO      | N/A |

OTHER PUBLICATIONS

Matthew Hartensveld, “Fully Monolithic GaN  $\mu$ LED Display System”, SID Society for Information Display, Jun. 28, 2021, pp. 880-883, vol. 52, Issue 1, <https://doi.org/10.1002/sdtp.14825>. cited by applicant

Authorized Officer Kari Rodriguez, International Search Report and Written Opinion mailed on Oct. 27, 2022 issued in PCT Patent Application No. PCT/US2022/035149. cited by applicant

Office Action and English Translation thereof issued on Feb. 5, 2025 in related Korean Patent Application No. 10-2024-7002808. cited by applicant

Office Action and English Translation thereof issued on Jan. 7, 2025 in related Japanese Patent Application No. 2023-579809. cited by applicant

## Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS (1) This case claims priority of U.S. Provisional Patent Application 63/215,776 entitled “Monolithically Integrated Top-Gate Thin-Film Transistor and LED,” filed Jun. 28, 2021, which is incorporated herein by reference in its entirety. If there are any contradictions or inconsistencies in language between this application and one or more of the cases that have been incorporated by reference that might affect the interpretation of the claims in this case, the claims in this case should be interpreted to be consistent with the language in this case.

### TECHNICAL FIELD

(1) The present disclosure relates to image display technology and, more particularly, to LED-based microdisplays.

### BACKGROUND

(2) Inorganic light-emitting diodes (LED) are robust, have long lifetimes, and can emit brighter light than other types of LED, such as organic light-emitting diodes (OLED). As a result, they are attractive for use as pixel elements in emissive displays and microdisplays.

(3) Historically, however, it has been difficult to integrate inorganic LED with the pixel drive circuitry in the backplane of a display. Inorganic LEDs are generally made with compound semiconductor material including group III-V or II-VI materials, for example, Gallium Nitride (GaN). Compound semiconductor materials require very high temperature for processing (>700 C). The drivers made using compound semiconductor technology exhibit significantly higher voltages compared to the standard silicon technology such as complimentary metal-oxide semiconductor (CMOS) with single crystal silicon or thin-film transistors (TFT) using amorphous silicon (aSi) or polycrystalline silicon (poly-Si). As a result, the fabrication of a practical display device using just GaN has been challenging.

(4) While there have been attempts to monolithically combine inorganic LEDs with standard silicon-based transistor technology to realize displays, they have been largely unsuccessful. For example, Hartensveld disclosed the hetero-epitaxial integration of GaN-based microLEDs on a silicon substrate in “Fully Monolithic GaN  $\mu$ LED Display System,” *Proceedings of Display Week 2021* published by the Society for Information Display, paper 61-5, held online May 17-21, 2021, which is incorporated herein by reference. Unfortunately, the cost and complexity of such monolithic integration technology is prohibitive for its use in many applications.

(5) Heterogeneous integration of inorganic LEDs and silicon-based electronics offers an alternative approach to monolithic integration. Such approaches employ pick-and-place technology to transfer arrays of fully formed LEDs from a bulk LED substrate to receiving substrates containing previously formed silicon transistor circuitry, where solder-bump bonding, or thermoset resin containing conductive particles, is used to operatively couple the LEDs and the circuitry. Unfortunately, long-term reliability and production-yield issues continue to be difficult to overcome.

(6) More recently, inorganic LED monolithically integrated with TFT circuitry has been demonstrated. For example, successful integration of bottom-gate TFT circuitry with inorganic LEDs was disclosed by Gosh in U.S. Pat. No. 9,793,252, issued Oct. 17, 2017, which is incorporated herein by reference. Unfortunately, the complicated layer stack structure of such structures gives rise to challenging fabrication issues that continue to impede adoption of this

technology in many applications.

(7) Inorganic LEDs and TFT transistor-based circuitry that are monolithically integrated in a practical and cost-effective manner would represent a significant advance over the prior art.

#### SUMMARY

(8) The present disclosure is directed to monolithic integration of top-gate TFT circuitry and inorganic LEDs. Embodiments in accordance with the present disclosure are particularly well-suited for use in displays, microdisplays, augmented-reality systems, and virtual-reality systems.

(9) An advance over the prior art is realized by forming a display whose pixels include a TFT having a top-gate architecture that is disposed directly on an LED, where the layer structure of the devices is combined. As a result, the combined layer structure of the circuitry and LEDs is significantly simplified and easier to fabricate, thereby reducing manufacturing costs and offering improved yield.

(10) An illustrative embodiment comprises a top-gate TFT that is formed directly on the top of an inorganic LED structure. The TFT and LED are monolithically integrated on a sapphire substrate. In order to enable formation of the TFT on top of the LED, the topography of the LED is accommodated by the inclusion of a planarization layer that includes dielectric material. The planarization layer is formed over the LED structure and polished back such that its top surface is coplanar with the top surface of the anode of the LED, which is simultaneously exposed. Once the planarization layer is formed and the top surface of the anode is exposed, the source and drain of the TFT are formed such that the drain resides on the anode and they are in electrical communication. The transistor structure is then completed by deposition of conformal layers of semiconductor and dielectric material that define the channel region and gate dielectric of the TFT. A gate electrode is then formed on the top of the gate dielectric to complete the monolithically integrated structure of the TFT and LED.

(11) Since the TFT is formed such that its drain is disposed on and in physical contact with the anode of the underlying LED, pixels and sub-pixels in accordance with the present disclosure can be scaled down to sizes that, heretofore, were impossible using prior-art approaches. By scaling the pixels and sub-pixels to extremely small dimensions, they can be used large-format displays, standard-resolution displays, or near-eye displays.

(12) In some embodiments, the anode of the LED and one of the drain or source of the TFT are formed of the same layer. In some embodiments, the anode of the LED functions as the drain or source of the TFT.

(13) In some embodiments, a storage capacitor is also monolithically integrated with the TFT and LED structures by forming it directly above the gate of the TFT. In some embodiments, the gate of the TFT functions as one plate of the storage capacitor.

(14) An embodiment in accordance with the present disclosure is a display comprising a first pixel that includes: a first light-emitting diode (LED) that includes a first cathode and a first anode; and a first thin-film transistor (TFT) disposed on the first LED, wherein the first TFT includes a first source, a first drain, and a first gate that is distal to a substrate; wherein the first LED and the first TFT are monolithically integrated on the substrate such that one of the first cathode and first anode is electrically coupled with one of the first source and the first drain.

(15) Another embodiment in accordance with the present disclosure is a display comprising a plurality of pixels, wherein each pixel of the plurality of pixels includes: a light-emitting diode (LED) that includes a cathode and an anode, the LED being disposed on a substrate, and one of the cathode and anode having a first surface that is distal to the substrate; a planarization layer having a second surface that is coplanar with the first surface, the planarization layer comprising a dielectric material; and a thin-film transistor (TFT) disposed on the LED and the planarization layer, wherein the TFT includes a source, a drain, and a gate that is distal to the substrate, and wherein one of the source and drain is electrically coupled with one of the anode and the cathode, and further wherein the other one of the source and drain is disposed on the planarization layer; wherein the plurality of

LEDs and the plurality of TFTs are monolithically integrated on the substrate.

(16) Yet another embodiment in accordance with the present disclosure is a method for forming a display that includes a plurality of pixels, the method including: forming a plurality of light-emitting diodes (LEDs) on a substrate, wherein each LED of the plurality thereof includes a cathode and an anode, one of the cathode and anode having a first surface that is distal to the substrate; forming a planarization layer comprising a dielectric material, the planarization layer having a second surface that is coplanar with the plurality of first surfaces; and forming a plurality of thin-film transistors (TFTs) such that each TFT of the plurality thereof is disposed on a different LED of the plurality of LEDs, wherein each TFT of the plurality thereof includes a source, a drain, and a gate that is distal to the substrate; wherein each TFT is formed such that (1) one of the first source and first drain is disposed on and electrically connected with one of the first anode and first cathode of its respective LED and (2) the other one of the source and drain is disposed on the second surface.

---

## Description

### BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIGS. 1A-B depict schematic drawings of perspective and cross-sectional views of a portion of a pixel suitable for use in an emissive display in accordance with the present disclosure.

(2) FIG. 2 depicts operations of a method suitable for forming a sub-pixel of a pixel of a display in accordance with the present disclosure.

(3) FIG. 3A depicts a schematic drawing of a cross-sectional view of nascent sub-pixel **100'** after the completion of LED **102**.

(4) FIG. 3B depicts a schematic drawing of a cross-sectional view of nascent sub-pixel **100'** after the completion of planarization layer **120**.

(5) FIG. 3C depicts a schematic drawing of a cross-sectional view of nascent sub-pixel **100'** after the completion of TFT **104**.

(6) FIG. 4A shows a schematic drawing of the electrical layout of a pixel of a display, the pixel including red, green, and blue sub-pixels, in accordance with the present disclosure.

(7) FIG. 4B shows a schematic drawing of cross-sectional view of the layer structure of the electrical-bus regions of sub-pixels **100R**, **100G**, and **100B**.

(8) FIG. 5 shows a schematic drawing of a more detailed perspective view of the layer structure of circuit portion **400**.

(9) FIG. 6 depicts a schematic drawing of a sub-pixel that includes a monolithically integrated storage capacitor in accordance with the present disclosure.

### DETAILED DESCRIPTION

(10) The following merely illustrates the principles of the disclosure. It will thus be appreciated that those skilled in the art will be able to devise various arrangements which, although not explicitly described or shown herein, embody the principles of the disclosure and are included within its spirit and scope.

(11) Furthermore, all examples and conditional language recited herein are principally intended expressly to be only for pedagogical purposes to aid the reader in understanding the principles of the disclosure and the concepts contributed by the inventor(s) to furthering the art, and are to be construed as being without limitation to such specifically recited examples and conditions.

(12) Moreover, all statements herein reciting principles, aspects, and embodiments of the disclosure, as well as specific examples thereof, are intended to encompass both structural and functional equivalents thereof. Additionally, it is intended that such equivalents include both currently known equivalents as well as equivalents developed in the future, i.e., any elements developed that perform the same function, regardless of structure.

(13) Thus, for example, it will be appreciated by those skilled in the art that any block diagrams herein represent conceptual views of illustrative circuitry embodying the principles of the disclosure. Similarly, it will be appreciated that any flow charts, flow diagrams, state transition diagrams, pseudo code, and the like represent various processes which may be substantially represented in computer readable medium and so executed by a computer or processor, whether or not such computer or processor is explicitly shown.

(14) The functions of the various elements shown in the Drawing, including any functional blocks that may be labeled as “processors”, may be provided through the use of dedicated hardware as well as hardware capable of executing software in association with appropriate software. When provided by a processor, the functions may be provided by a single dedicated processor, by a single shared processor, or by a plurality of individual processors, some of which may be shared. Moreover, explicit use of the term “processor” or “controller” should not be construed to refer exclusively to hardware capable of executing software, and may implicitly include, without limitation, digital signal processor (DSP) hardware, network processor, application specific integrated circuit (ASIC), field programmable gate array (FPGA), read-only memory (ROM) for storing software, random access memory (RAM), and non-volatile storage. Other hardware, conventional and/or custom, may also be included.

(15) Software modules, or simply modules which are implied to be software, may be represented herein as any combination of flowchart elements or other elements indicating performance of process steps and/or textual description. Such modules may be executed by hardware that is expressly or implicitly shown.

(16) Unless otherwise explicitly specified herein, the figures comprising the drawing are not drawn to scale.

(17) As noted above, monolithic integration of top-gate TFT circuitry and inorganic LEDs for use in display and microdisplay applications affords embodiments in accordance with the present disclosure with significant advantages over the prior art. First, the combined layer structure of the circuitry and LEDs is significantly simplified. Second, such a design is significantly easier to fabricate, reducing manufacturing costs and offering improved system yield. Third, the layer stacks of the TFT and LED are substantially independent from one another. As a result, neither needs to be compromised due to the inclusion of the other.

(18) FIGS. 1A-B depict schematic drawings of perspective and cross-sectional views of a portion of a pixel suitable for use in an emissive display in accordance with the present disclosure. Sub-pixel **100** includes LED **102** and TFT **104**, which are monolithically integrated on substrate **106**.

(19) For the purposes of this Specification, including the appended claims, the term “monolithically integrated” is defined as formed either: in the body of a substrate, typically by etching into the substrate or; on the surface of the substrate, typically by patterning layers disposed on the surface. The term monolithically integrated explicitly excludes systems/devices that have been integrated using hybrid integration methods, such as the joining of fully formed devices using processes such as gluing, solder-bump bonding, and the like.

(20) FIG. 2 depicts operations of a method suitable for forming a sub-pixel of a pixel of a display in accordance with the present disclosure. Method **200** begins with operation **201**, wherein LED **102** is formed on substrate **106**.

(21) Substrate **106** is a substrate suitable for use in a planar-processing fabrication method. Preferably, substrate **106** is substantially transparent for the light emitted by LED **102**. In the depicted example, substrate **106** is a sapphire substrate; however, other substrates suitable for use in accordance with the present disclosure will be apparent to one skilled in the art, after reading this Specification.

(22) LED **102** is an inorganic LED structure that is epitaxially grown on substrate **106**. LED **102** comprises, among other layers, semiconductor (SC) layer **108**, gain layer **110**, SC layer **112**, cathode **116**, and anode **118**. Typically, the semiconductor and gain layers of LED **102** are

epitaxially grown using metal-organic chemical vapor deposition (MOCVD); however, any suitable growth method can be used to form the layers of LED **102**, including atomic layer epitaxy (ALE), molecular beam epitaxy (MBE), and the like.

(23) The formation of LED **102** begins with the epitaxial growth of n-type semiconductor (SC) layer **108** on substrate **106**. SC layer **108** functions as an electrically conductive layer that enables electrical connection to cathode **116**. It also functions as a lower optical confinement layer for gain layer **110**. In the depicted example, SC layer **108** is a layer of n-doped gallium nitride (GaN) having a thickness of approximately 2 microns; however, in some embodiments, SC layer **108** includes a different compound-semiconductor material and/or thickness.

(24) Gain layer **110** is then grown on SC layer **108**. Gain layer **110** comprises one or more layers of compound semiconductor material suitable for providing optical gain within the structure of LED **102**. In the depicted example, gain layer **110** is a multiple quantum well (MQW) layer comprising alternating layers of indium gallium nitride (InGaN) and gallium nitride (GaN) having a collective thickness of approximately 150 nm; however, in some embodiments, gain layer **110** includes at least one different compound-semiconductor material and/or has a different thickness.

(25) The formation of LED **102** then continues with the epitaxial growth of SC layer **112** on gain layer **110**. SC layer **112** functions as a top contact for LED **102** and as an upper optical confinement layer for the gain layer. In the depicted example, SC layer **112** is a layer of p-doped GaN having a thickness of approximately 250 nm; however, in some embodiments, SC layer **112** includes a different compound semiconductor and/or has a different thickness.

(26) Gain layer **110** and SC layer **112** are then patterned to define mesa **114**, which exposes a region of SC layer **108** in preparation for the formation of cathode **116**.

(27) Cathode **116** is formed on SC layer **108** such that the cathode is electrically coupled with gain layer **110** through SC layer **108**. In the depicted example, cathode **116** is a layer of molybdenum (Mo) having a thickness of approximately 50 nm. Typically, cathode **116** is formed via direct patterning by sputtering through a shadow mask; however, any suitable deposition and/or deposition and patterning methods can be used to form cathode **116**.

(28) In similar fashion, anode **118** is then formed on SC layer **112** such that the anode is electrically coupled with gain layer **110** through SC layer **112**. In the depicted example, anode **118** is a layer of molybdenum (Mo) having a thickness of approximately 20 nm.

(29) FIG. 3A depicts a schematic drawing of a cross-sectional view of nascent sub-pixel **100'** after the completion of LED **102**.

(30) Once LED **102** is complete, method **200** continues with operation **202**, wherein planarization layer **120** is formed over the LED structure. Planarization layer **120** is a layer of dielectric material that fills the regions surrounding mesa **114**. In the depicted example, planarization layer **120** comprises silicon dioxide that is vapor deposited over the topography of LED **102**. In some embodiments, planarization layer **120** is deposited in a manner other than vapor deposition, such as spin coating, spray coating, and the like.

(31) At operation **203**, planarization layer **120** is thinned to expose the top surface (i.e., surface **S1**) of anode **118**. As a result, surface **S2** (i.e., the top surface of planarization layer **120**) is substantially coplanar with surface **S1** and defines a flat surface suitable for the formation of the layers of TFT **104** using planar processing technologies. In the depicted example, planarization layer **120** is thinned and planarized via chemical-mechanical polishing (CMP); however, any suitable method can be used without departing from the scope of the present disclosure.

(32) FIG. 3B depicts a schematic drawing of a cross-sectional view of nascent sub-pixel **100'** after the completion of planarization layer **120**.

(33) At operation **204**, TFT **104** is formed on substrate **106**.

(34) TFT **104** is a FET transistor structure that is configured such that its gate is distal to LED **102**. TFT **104** includes gate **122**, drain **124**, source **126**, semiconductor layer **128**, and gate dielectric **130**.

(35) The formation of TFT **104** begins with formation of drain **124** on anode **118** and source **126** on the top surface of planarization layer **120**. Typically, drain **124** and source **126** are formed in the same operation using methods analogous to those described above and respect to the formation of cathode **116**. In the depicted example, each of drain **124** and source **126** is a layer of molybdenum having a thickness of approximately 20 nm.

(36) After the definition of drain **124** and source **126**, SC layer **128** is deposited over them using a conformal deposition method such that its material resides between the source and drain. In the depicted example, SC layer **128** is a layer of indium gallium zinc oxide (IGZO) having a thickness of approximately 40 nm.

(37) Gate dielectric **130** is then formed on SC layer **128**. In the depicted example, gate dielectric **130** is a layer of silicon dioxide having a thickness of approximately 150 nm.

(38) The formation of TFT **104** is completed with the definition of gate **122** on the top surface of gate dielectric **130**. In the depicted example, gate **122** includes a layer of molybdenum having a thickness of approximately 20 nm.

(39) As will be apparent to one skilled in the art after reading this Specification, however, any suitable thickness and/or material can be used for any of the constituent layers/structures of TFT **104** without departing from the scope of the present disclosure.

(40) As will also be apparent to one skilled in the art, in some embodiments, sub-pixel **100** typically includes additional semiconductor layers (e.g., buffer layers, contact-enhancement layers, etc.), as well as additional features, such as vias, bond pads, and electrical traces that enable its electrical connection to other sub-pixels, control circuitry, drive circuitry and the like. For clarity, these layers/features are not shown in the depicted example.

(41) FIG. 3C depicts a schematic drawing of a cross-sectional view of nascent sub-pixel **100'** after the completion of TFT **104**.

(42) At operation **205**, passivation layer **132** is formed to electrically passivate LED **102** and TFT **104**, thereby completing sub-pixel **100**.

(43) Upon completion of sub-pixel **100**, TFT **104** and LED **102** are electrically coupled via drain **124** and anode **118**, which are formed such that the drain is in physical contact with the anode. In some embodiments, anode **118** and drain **124** are defined by a single element within the structure of TFT **104**.

(44) FIG. 4A shows a schematic drawing of the electrical layout of a pixel of a display, the pixel including red, green, and blue sub-pixels, in accordance with the present disclosure. Display portion **400** depicts pixel P1, which is one pixel of a display comprising a plurality of substantially identical pixels. Pixel P1 includes three sub-pixels **100R**, **100G**, and **100B**, bus **402**, and bus **404**.

(45) FIG. 4B shows a schematic drawing of cross-sectional view of the layer structure of the electrical-bus regions of sub-pixels **100R**, **100G**, and **100B**. Layer structure **406** depicts only bus **402** and bus **404**, as well as the interlayer dielectric that resides between them to provide electrical isolation.

(46) Each of sub-pixels **100R**, **100G** and **100B** includes, among other circuit elements, an LED **102** that is configured to emit the desired color of that sub-pixel, as well as TFT **104**, which are electrically connected as discussed above and with respect to FIGS. 1A-B. In other words, sub-pixels **100R**, **100G** and **100B** include LED **102R**, **104G**, and **104B**, respectively, where LED **102R** emits red light, LED **102R** emits green light, and LED **102B** emits blue light.

(47) In each of sub-pixels **100R**, **100G**, and **100B**, LED cathode **116** is electrically connected to electrical bus **402**, which is held at a common VSS voltage level. In similar fashion, in each sub-pixel, the source of its respective drive-transistor **104** is electrically connected to electrical bus **404**, which is held at a common ELVDD voltage level.

(48) In the depicted example, bus **402** is formed at the same time as cathode **116**; however, bus **402** can be formed in a separate process without departing from the scope of the present disclosure.

(49) In similar fashion, in the depicted example, bus **404** is formed at the same time as drain **124**



and source **126**; however, bus **404** can be formed in a separate process without departing from the scope of the present disclosure.

(50) Bus **402** is electrically isolated from bus **404** by a portion of planarization layer **120**, which functions as an interlayer dielectric. In some embodiments, a different dielectric layer is included to electrically isolate bus **402** and bus **404**.

(51) FIG. 5 shows a schematic drawing of a more detailed perspective view of the layer structure of circuit portion **400**. As is common to most LED-based displays, data lines Data R, Data G, and Data B are common to all of the pixels in the same row of the display. Typically, the data lines and gates of each sub-pixel are separated by a thick layer of electrical insulator (i.e., insulator **504**). In some embodiments, insulator **504** includes passivation layer **132**.

(52) In the prior art, each pixel (or sub-pixel) typically includes a storage capacitor that is located adjacent to the transistor and LED. In other words, the circuit elements included in the pixel drive circuitry is horizontally arranged. As a result, each circuit element requires a significant amount of chip real estate, which places a lower limit on how small each pixel can be (and a commensurate upper limit on pixel density).

(53) It is aspect of the present disclosure, however, that a storage capacitor can be formed on top of a TFT to realize a vertical arrangement of elements, thereby reducing the real estate required for a given pixel drive circuit.

(54) FIG. 6 depicts a schematic drawing of a sub-pixel that includes a monolithically integrated storage capacitor in accordance with the present disclosure. Sub-pixel **600** comprises sub-pixel **100** and capacitor **602**.

(55) Capacitor **602** is a parallel plate capacitor that includes capacitor plates C1 and C2, which are located on either side of dielectric **604**. Capacitor **602** is formed on sub-pixel **100** such that plate C1 is in physical and electrical contact with gate **122**.

(56) Each of capacitor plates C1 and C2 is analogous to cathode **116** described above. In the depicted example, each capacitor plate is a layer of molybdenum having a thickness of approximately 50 nm.

(57) Dielectric **604** is analogous to gate dielectric **130** described above. In the depicted example, dielectric **604** is a layer of silicon dioxide having a thickness of approximately 150 nm.

(58) Although not depicted, typically, a planarization layer analogous to planarization layer **120** is formed over sub-pixel **100** prior to the formation of plate C1.

(59) By forming sub-pixel **600** such that capacitor **602** is disposed on top of TFT **104**, embodiments in accordance with the present disclosure are afforded significant advantages over the prior art, including: i. reduced pixel area required for circuitry; or ii. greater pixel density; or iii. increased circuit complexity without sacrificing pixel density; or iv. a larger capacitor, enabling better storage performance; or v. any combination of i, ii, iii, and iv.

(60) It is to be understood that the disclosure teaches some examples of the illustrative embodiment and that many variations of the invention can easily be devised by those skilled in the art after reading this disclosure.

## Claims

1. A display comprising a first pixel that includes: a first light-emitting diode (LED) that includes a first cathode and a first anode, wherein one of the first cathode and first anode includes a first surface; a planarization layer having a second surface, wherein the second surface is substantially coplanar with the first surface; and a first thin-film transistor (TFT) disposed on the first LED, wherein the first TFT includes a first source, a first drain, and a first gate that is distal to a substrate, and wherein one of the first source and first drain is disposed on and in direct physical contact with the first surface, and further wherein the other one of the first source and first drain is in direct physical contact with the second surface; wherein the first LED and the first TFT are

- monolithically integrated on the substrate such that the one of the first cathode and first anode is directly electrically connected with the one of the first source and the first drain; and wherein the TFT is disposed on the LED such that the layer structures of the TFT and LED are combined.
2. The display of claim 1 wherein the first source is disposed on and in direct physical and electrical contact with the first surface.
  3. The display of claim 1 wherein the first drain is disposed on and in direct physical and electrical contact with the first surface.
  4. The display of claim 3 wherein the first anode and the first drain are the same element such that the first anode is configured to function as the first drain.
  5. The display of claim 1 wherein the first pixel further comprises a parallel-plate capacitor having a first plate, a second plate, and a dielectric layer disposed between the first and second plates, and wherein the first plate is electrically coupled with the first gate, and wherein the first plate is disposed on and in physical contact with the first gate.
  6. The display of claim 5 wherein the first gate and the first plate are the same element such that the first gate is configured to function as the first plate.
  7. The display of claim 1, wherein the first pixel further includes: a second LED that includes a second cathode and a second anode; and a second TFT disposed on the second LED, wherein the second TFT includes a second source, a second drain, and a second gate that is distal to the substrate; wherein the second LED and the second TFT are monolithically integrated on the substrate such that one of the second cathode and second anode is electrically coupled with one of the second source and the second drain.
  8. A display comprising a plurality of pixels, wherein each pixel of the plurality of pixels includes: a light-emitting diode (LED) that includes a cathode and an anode, the LED being disposed on a substrate, and one of the cathode and anode having a first surface that is distal to the substrate; a planarization layer having a second surface that is coplanar with the first surface, the planarization layer comprising a dielectric material; and a thin-film transistor (TFT) disposed on the LED and the planarization layer, wherein the TFT includes a source, a drain, and a gate that is distal to the substrate, and wherein one of the source and drain is disposed on and in direct physical and electrical contact with the first surface; wherein the LED and TFT of each pixel of the plurality of pixels are monolithically integrated on the substrate; and wherein, within each pixel of the plurality of pixels, its respective TFT is disposed on its respective LED such that their layer structures are combined.
  9. The display of claim 8 wherein the anode and the drain are in direct physical contact and electrically connected.
  10. The display of claim 9 wherein the anode and the drain are the same element such that the anode functions as the drain.
  11. The display of claim 8 wherein each pixel further comprises a parallel-plate capacitor having a first plate, a second plate, and a dielectric layer disposed between the first and second plates, and wherein the first plate is electrically coupled with the gate, and wherein the first plate is disposed on and in physical contact with the gate.
  12. The display of claim 11 wherein the first gate and the first plate are the same element such that the first gate is configured to function as the first plate.
-