

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12405422
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Chern; Chan-Hong

Cladding structure for semiconductor waveguide

Abstract

A semiconductor structure including a semiconductor waveguide layer over a second dielectric layer and between sidewalls of a first dielectric layer. A first cladding layer is between the sidewalls of the first dielectric layer and directly over the semiconductor waveguide layer. A second cladding layer is between sidewalls of the second dielectric layer and directly under the semiconductor waveguide layer. A difference between a refractive index of the semiconductor waveguide layer and a refractive index of the first cladding layer is less than a difference between the refractive index of the semiconductor waveguide layer and a refractive index of the first dielectric layer. A difference between the refractive index of the semiconductor waveguide layer and a refractive index of the second cladding layer is less than a difference between the refractive index of the semiconductor waveguide layer and a refractive index of the second dielectric layer.

Inventors:	Chern; Chan-Hong (Palo Alto, CA)
Applicant:	Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)
Family ID:	89969369
Assignee:	Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)
Appl. No.:	17/895342
Filed:	August 25, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20240069278 A1	Feb. 29, 2024

Publication Classification

Int. Cl.: G02B6/122 (20060101); G02B6/12 (20060101); G02B6/132 (20060101); G02B6/136 (20060101)

U.S. Cl.:

CPC **G02B6/1223** (20130101); **G02B6/1228** (20130101); **G02B6/132** (20130101);
G02B6/136 (20130101); G02B2006/12195 (20130101)

Field of Classification Search

CPC: G02B (2006/12176); G02B (6/1228); G02B (6/1223); G02B (6/132); G02B (6/136);
 G02B (2006/12195)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2004/0037497	12/2003	Lee	385/28	G02B 6/132
2007/0274654	12/2006	Choudhury et al.	N/A	N/A
2010/0086255	12/2009	Ishizaka	N/A	N/A
2018/0074259	12/2017	Hickey	N/A	G02B 6/1221
2022/0057577	12/2021	Chern et al.	N/A	N/A
2023/0244034	12/2022	Malik	385/14	G02B 6/1228

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
201130117	12/2010	TW	N/A
2021178727	12/2020	WO	N/A

OTHER PUBLICATIONS

Tsuchizawa et al. "Spot-Size Converters for Rib-Type Silicon Photonic Wire Waveguides" 2008 5th IEEE International Conference on Group IV Photonics, published on Oct. 7, 2008. cited by applicant

Primary Examiner: Hollweg; Thomas A

Assistant Examiner: Endresen; Kirsten D.

Attorney, Agent or Firm: Eschweiler & Potashnik, LLC

Background/Summary

BACKGROUND

(1) Optical waveguides are often used as components in integrated optical circuits. Optical waveguides are used to confine and guide light from a first point on an integrated chip (IC) to a second point on the IC with minimal attenuation. Many modern optical waveguides are formed using semiconductors. A semiconductor waveguide may include an optical converter or an optical coupler for optically coupling an optical fiber to the semiconductor waveguide.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.
- (2) FIG. 1A and FIG. 1B illustrate cross-sectional views of some embodiments of a semiconductor structure comprising a semiconductor waveguide layer, a first cladding layer over the semiconductor waveguide layer, and a second cladding layer under the semiconductor waveguide layer.
- (3) FIG. 1C illustrates a top view of some embodiments of the semiconductor structure of FIG. 1A and FIG. 1B.
- (4) FIG. 1D illustrates a three-dimensional view of some embodiments of the semiconductor structure of FIGS. 1A-1C.
- (5) FIG. 2 illustrates a cross-sectional view of some embodiments of the semiconductor structure of FIG. 1A in which a thickness of the second cladding layer is different than the thickness of the first cladding layer.
- (6) FIG. 3 illustrates a cross-sectional view of some embodiments of the semiconductor structure of FIG. 1A in which a top surface of the second cladding layer is wider than a bottom surface of the second cladding layer.
- (7) FIG. 4A and FIG. 4B illustrate cross-sectional views of some embodiments of the semiconductor structure of FIG. 1A and FIG. 1B, respectively, in which a plurality of conductive interconnects are disposed directly over the first cladding layer, the semiconductor waveguide layer, and the second cladding layer.
- (8) FIG. 5A and FIG. 5B illustrate cross-sectional views of some embodiments of the semiconductor structure of FIG. 1A and FIG. 1B, respectively, in which a buffer layer is directly between the semiconductor waveguide layer and the first cladding layer.
- (9) FIG. 6A and FIG. 6B illustrate cross-sectional views of some embodiments of the semiconductor structure of FIG. 5A and FIG. 5B, respectively, in which the buffer layer separates the first dielectric layer from the second dielectric layer.
- (10) FIG. 7A and FIG. 7B illustrate cross-sectional views of some embodiments of the semiconductor structure of FIG. 5A and FIG. 5B, respectively, in which the buffer layer is directly between the semiconductor waveguide layer and the second cladding layer.
- (11) FIG. 8A and FIG. 8B illustrate cross-sectional views of some embodiments of the semiconductor structure of FIG. 7A and FIG. 7B, respectively, in which the buffer layer separates the first dielectric layer from the second dielectric layer.
- (12) FIG. 9 and FIG. 10 illustrate cross-sectional views of some embodiments of the semiconductor structure of FIG. 1A in which a first buffer layer is directly between the semiconductor waveguide layer and the first cladding layer and a second buffer layer is directly between the semiconductor waveguide layer and the second cladding layer.
- (13) FIGS. 11A-32A illustrate cross-sectional views and FIGS. 11B-32B illustrate corresponding three-dimensional views of some embodiments of a method for forming a semiconductor structure comprising a semiconductor waveguide layer, a first cladding layer along a first side of the semiconductor waveguide layer, and a second cladding layer along a second side of the semiconductor waveguide layer.
- (14) FIG. 33 illustrates a flow diagram of some embodiments of a method for forming a semiconductor structure comprising a semiconductor waveguide layer, a first cladding layer along a first side of the semiconductor waveguide layer, and a second cladding layer along a second side of the semiconductor waveguide layer.

DETAILED DESCRIPTION

(15) The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(16) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(17) Some modern integrated chips include optical structures. For example, an integrated chip includes an optical waveguide layer for guiding optical radiation. The optical waveguide layer comprises a semiconductor material and is disposed over a buried dielectric layer of a semiconductor-on-insulator (SOI) substrate. An optical fiber may be coupled to the optical waveguide layer. A mode size (e.g., the size of the electric field distribution) in the optical fiber is substantially greater than a mode size in the optical waveguide layer. Thus, the optical waveguide layer may include a spot-size converter (SSC) for expanding the mode size along the optical waveguide layer to match the mode size of the optical fiber. The SSC is formed by a tapered segment of the optical waveguide layer which tapers to a waveguide tip. The mode size in the optical waveguide layer expands along the taper as the taper approaches the tip. Ideally, the mode size expansion at the tip is large enough that the mode size of the optical waveguide layer at the tip matches the mode size of the optical fiber.

(18) In some devices, the expansion of the mode size at the tip depends, in part, on the size of the optical waveguide layer at the tip. For example, as the dimensions (e.g., the width and/or the thickness) of the waveguide tip are reduced, and the expansion of the mode size at the tip is increased. Thus, to achieve substantially large mode size expansion at the waveguide tip so that the mode size at the waveguide tip matches the mode size of the optical fiber, the taper must narrow to a substantially small tip.

(19) However, forming a taper having a tip with such small dimensions can be challenging. For example, because the waveguide tip is formed to have such small dimensions, even minor variations in the fabrication process can result in relatively substantial variations in size of the waveguide tip which can cause substantial variations in the mode size expansion at the waveguide tip. Substantial variations in the mode size expansion at the waveguide tip can cause substantial variations in a coupling efficiency between the optical waveguide layer and the optical fiber. As a result, a performance of the optical waveguide layer may be reduced.

(20) Various embodiments of the present disclosure are related to a semiconductor structure comprising a semiconductor waveguide layer which tapers to a tip, where the tip is surrounded by a first cladding layer and a second cladding layer to improve a performance of the semiconductor structure. For example, the first cladding layer is disposed directly over the tip of the semiconductor waveguide layer and on opposite sides of the semiconductor waveguide layer. The second cladding layer is disposed directly under the tip of the semiconductor waveguide layer. An optical fiber can be optically coupled to the semiconductor waveguide layer at the tip. The first

cladding layer and the second cladding layer have refractive indices that are substantially similar to the refractive index of the semiconductor waveguide layer.

(21) The expansion of the mode size of the semiconductor waveguide layer at the tip of the semiconductor waveguide layer is affected by both the size of the tip and the materials surrounding the tip. For example, as the difference between the refractive index of the semiconductor waveguide layer and the refractive index of the surrounding layers is reduced, the expansion of the mode size at the tip is increased. Thus, by surrounding the tip of the semiconductor waveguide layer with the first and second cladding layers having refractive indices that are substantially similar to the refractive index of the semiconductor waveguide layer, the dimensional requirements of the tip can be relaxed (e.g., the size of the tip can be increased) without reducing a mode field expansion at the tip. By relaxing the dimensional requirements of the tip, variations in the fabrication of the tip may have a reduced impact on the resulting size of the waveguide tip. Thus, a relative precision and/or accuracy of the tip may be improved. As a result, a coupling efficiency between the semiconductor waveguide layer and the optical fiber may be improved.

(22) FIG. 1A illustrates a cross-sectional view **100a** of some embodiments of a semiconductor structure comprising a semiconductor waveguide layer **102**, a first cladding layer **104** over the semiconductor waveguide layer **102**, and a second cladding layer **106** under the semiconductor waveguide layer **102**. In some embodiments, the cross-sectional view **100a** of FIG. 1A is illustrated in an x-z plane formed by x-axis **101x** and z-axis **101z**. In some embodiments, the cross-sectional view **100a** of FIG. 1A may, for example, be taken across line A-A' of FIG. 1C.

(23) The semiconductor structure includes a first dielectric layer **108**. The first dielectric layer **108** comprises a first dielectric having a first refractive index. A second dielectric layer **110** is under the first dielectric layer **108**. The second dielectric layer **110** comprises a second dielectric having a second refractive index. The semiconductor waveguide layer **102** is over the second dielectric layer **110**. The semiconductor waveguide layer **102** tapers to a tip **102a** (e.g., as shown in FIGS. 1C, 1D). The tip **102a** of the semiconductor waveguide layer **102** is directly between first sidewalls **108a** of the first dielectric layer **108**. The semiconductor waveguide layer **102** comprises a semiconductor having a third refractive index.

(24) In some embodiments, an optical fiber **112** is arranged adjacent to the tip **102a** and is optically coupled to the semiconductor waveguide layer **102** at the tip **102a**. A size of the optical fiber **112** (e.g., a diameter of a core of the optical fiber **112**) is substantially larger than the size (e.g., a height and/or a width) of the semiconductor waveguide layer **102**. Thus, a mode of the optical fiber **112** is substantially larger than a mode of the semiconductor waveguide layer **102**. Consequently, a substantially large mode size expansion must occur at the tip **102a** to match the mode size at the tip **102a** to the mode size of the optical fiber **112**.

(25) The first cladding layer **104** and the second cladding layer **106** surround the tip **102a** of the semiconductor waveguide layer **102**. For example, the first cladding layer **104** is directly between the first sidewalls **108a** of the first dielectric layer **108**, on opposite sides of the tip **102a**, and directly over the tip **102a**. The second cladding layer **106** is directly between first sidewalls **110a** of the second dielectric layer **110** and directly under the tip **102a**. The first cladding layer **104** comprises a third dielectric having a fourth refractive index. The second cladding layer **106** comprises a fourth dielectric having a fifth refractive index. The third dielectric and the fourth dielectric are different than the first dielectric and the second dielectric.

(26) A difference between the third refractive index and the fourth refractive index is less than a difference between the third refractive index and the first refractive index. Further, a difference between the third refractive index and the fifth refractive index is less than a difference between the third refractive index and the second refractive index. Furthermore, the fourth refractive index and the fifth refractive index are substantially similar to the third refractive index. For example, in some embodiments, both a difference between the refractive index of the semiconductor waveguide layer **102** (e.g., the third refractive index) and the refractive index of the first cladding layer **104** (e.g., the

fourth refractive index) and a difference between the refractive index of the semiconductor waveguide layer **102** (e.g., the third refractive index) and the refractive index of the second cladding layer **106** (e.g., the fifth refractive index) are less than 2, less than 1.8, less than 1.6, or some other suitable value.

(27) By surrounding the tip **102a** of the semiconductor waveguide layer **102** with the first and second cladding layers **104**, **106** having refractive indices that are substantially similar to the refractive index of the semiconductor waveguide layer **102**, the dimensional requirements of the tip **102a** can be relaxed (e.g., the size of the tip **102a** can be increased) without reducing a mode field expansion at the tip **102a**. By relaxing the dimensional requirements of the tip **102a**, variations in the fabrication of the tip **102a** may have a reduced impact on the resulting size of the tip **102a**. Thus, a relative precision and/or accuracy of the size of the tip **102a** may be improved. As a result, a coupling efficiency between the semiconductor waveguide layer **102** and the optical fiber **112** may be improved.

(28) FIG. **1B** illustrates another cross-sectional view **100b** of some embodiments of the semiconductor structure of FIG. **1A**. In some embodiments, the cross-sectional view **100b** of FIG. **1B** is illustrated in an y-z plane formed by y-axis **101y** and z-axis **101z**. In some embodiments, the cross-sectional view **100b** of FIG. **1B** may, for example, be taken across line B-B' of FIG. **1C**.

(29) The semiconductor waveguide layer **102** comprises a tapered transition segment **102b**, a slab transition segment **102c**, a tapered device segment **102d**, and a slab device segment **102e**. The tapered transition segment **102b** is between the slab transition segment **102c** and the tip **102a**. The slab transition segment **102c** is between the tapered transition segment **102b** and the tapered device segment **102d**. The tapered device segment **102d** is between the slab transition segment **102c** and the slab device segment **102e**.

(30) The first cladding layer **104** is directly over the tip **102a** and at least part of the tapered transition segment **102b**. In some embodiments, the first dielectric layer **108** is directly over part of the tapered transition segment **102b**. For example, in some embodiments, the first cladding layer **104** is on an top surface **102bt** of the tapered transition segment **102b** and the first dielectric layer **108** is on the top surface **102bt** of the tapered transition segment **102b**.

(31) The second cladding layer **106** is directly under the tip **102a** and at least part of the tapered transition segment **102b**. In some embodiments, the second dielectric layer **110** is directly under part of the tapered transition segment **102b**. For example, in some embodiments, the second cladding layer **106** is on a bottom surface **102bb** of the tapered transition segment **102b** and the second dielectric layer **110** is on the bottom surface **102bb** of the tapered transition segment **102b**.

(32) A sidewall **104a** of the first cladding layer **104** is directly over the semiconductor waveguide layer **102** (e.g., directly over the tapered transition segment **102b**) and a sidewall **106a** of the second cladding layer **106** is directly under the semiconductor waveguide layer (e.g., directly under the tapered transition segment **102b**). A second sidewall **108b** of the first dielectric layer **108** extends along the sidewall **104a** of the first cladding layer **104** and is directly over the semiconductor waveguide layer **102** (e.g., directly over the tapered transition segment **102b**). A second sidewall **110b** of the second dielectric layer **110** extends along the sidewall **106a** of the second cladding layer **106** and is directly under the semiconductor waveguide layer **102** (e.g., directly under the tapered transition segment **102b**).

(33) The first cladding layer **104** and the second cladding layer **106** surround the tip **102a** and the tapered transition segment **102b** to increase the mode size expansion at the tip **102a** where the semiconductor waveguide layer **102** is optically coupled to the optical fiber **112**. The first cladding layer **104** and the second cladding layer **106** do not surround the slab transition segment **102c**, the tapered device segment **102d**, and the slab device segment **102e** to reduce mode size expansion at these segments. Thus, a likelihood of optical radiation escaping the semiconductor waveguide layer **102** and the surrounding first and second dielectric layers **108**, **110** along these segments is reduced. As a result, a loss of optical radiation along the semiconductor waveguide layer **102** may

be reduced and hence a performance of the semiconductor waveguide layer **102** may be improved.

(34) FIG. **1C** illustrates a top view **100c** of some embodiments of the semiconductor structure of FIG. **1A** and FIG. **1B**. In some embodiments, the top view **100c** of FIG. **1C** is illustrated in an x-y plane formed by x-axis **101x** and y-axis **101y**. In some embodiments, the top view **100c** of FIG. **1C** may, for example, be taken across line A-A' of FIG. **1A** and/or line B-B' of FIG. **1B**.

(35) The first cladding layer **104** is on first sidewalls **102s** of the semiconductor waveguide layer **102** and the first dielectric layer **108** is on the first sidewalls **102s** of the semiconductor waveguide layer **102**. The first dielectric layer **108** is on opposite sides of the slab transition segment **102c**, the tapered device segment **102d**, and the slab device segment **102e**.

(36) A width (e.g., as measured along the x-axis **101x**) of the tapered transition segment **102b** is tapered along a length (e.g., as measured along the y-axis **101y**) of the tapered transition segment to the tip **102a**. A width of the slab transition segment **102c** is approximately uniform along its length. A width of the tapered device segment **102d** is tapered to a tip of the tapered device segment **102d**. A width of the slab device segment **102e** is approximately uniform along its length. In some embodiments, a lower portion of the semiconductor waveguide layer **102** is wider than an upper portion of semiconductor waveguide layer **102** along the slab device segment **102e**.

(37) FIG. **1D** illustrates a three-dimensional view **100d** of some embodiments of the semiconductor structure of FIGS. **1A-1C**.

(38) The tip **102a** and part of the tapered transition segment **102b** are surrounded by the first cladding layer **104** and the second cladding layer **106**. Other segments of the semiconductor waveguide layer **102** are surrounded by the first dielectric layer **108** and the second dielectric layer **110**.

(39) In some embodiments, the semiconductor waveguide layer **102** comprises silicon or some other suitable material. In some embodiments, a width (e.g., as measured along the x-axis **101x**) of the tip **102a** ranges from about 150 nanometers to 200 nanometers, 160 nanometers to 190 nanometers, or some other suitable range. In some embodiments, a thickness (e.g., as measured along the z-axis **101z**) of the tip **102a** ranges from about 150 nanometers to 250 nanometers, 175 nanometers to 225 nanometers, or some other suitable range. In some embodiments, a width of the slab transition segment **102c** ranges from about 600 nanometers to 1000 nanometers or some other suitable value and a thickness of the slab transition segment **102c** is approximately equal to the thickness of the tip **102a**. In some embodiments, a width of the slab device segment **102e** ranges from about 370 nanometers to 470 nanometers or some other suitable value and a thickness of the slab device segment **102e** ranges from about 250 nanometers to 350 nanometers or some other suitable range.

(40) In some embodiments, the first dielectric (e.g., of the first dielectric layer **108**) and/or the second dielectric (e.g., of the second dielectric layer **110**) comprise silicon dioxide or some other suitable material. In some embodiments, a thickness of the first dielectric layer **108** and/or the second dielectric layer **110** ranges from about 2 micrometers to 5 micrometers, 3 micrometers to 5 micrometers, or some other suitable range.

(41) The third dielectric (e.g., of the first cladding layer **104**) and/or the fourth dielectric (e.g., of the second cladding layer **106**) comprise some dielectric material(s) having a refractive index that is substantially similar to the refractive index of the semiconductor waveguide layer **102**. For example, in some embodiments, the third dielectric and/or the fourth dielectric may be or comprise silicon nitride, hafnium oxide, or some other suitable material. In some embodiments, the fourth dielectric is different than the third dielectric and the fifth refractive index (e.g., of the second cladding layer **106**) is different from the fourth refractive index (e.g., of the first cladding layer **104**). In some other embodiments, the fourth dielectric is the same as the third dielectric and thus the fifth refractive index is the same as the fourth refractive index. In some embodiments, a thickness of the first cladding layer **104** ranges from about 2 micrometers to 5 micrometers, 3 micrometers to 5 micrometers, or some other suitable range. In some embodiments, a thickness of

the second cladding layer **106** is approximately equal to the thickness of the first cladding layer **104**.

(42) FIG. 2 illustrates a cross-sectional view **200** of some embodiments of the semiconductor structure of FIG. 1A in which a thickness **106t** of the second cladding layer **106** is different than the thickness **104t** of the first cladding layer **104**.

(43) In some embodiments, the thickness **106t** of the second cladding layer **106** is less than the thickness **104t** of the first cladding layer **104**. For example, because the first cladding layer **104** is over and on opposite sides of the tip **102a** of the semiconductor waveguide layer **102**, a distance **202** between a top surface of the first cladding layer **104** and a center of the tip **102a** is less than the thickness **104t** of the first cladding layer **104**. Further, because the tip **102a** is over the second cladding layer **106**, a distance **204** between a bottom surface of the second cladding layer **106** and the center of the tip **102a** is greater than the thickness **106t** of the second cladding layer **106**. Thus, in some embodiments, the thickness **106t** of the second cladding layer **106** is less than the thickness **104t** of the first cladding layer so the distance **202** between the top surface of the first cladding layer **104** and the center of the tip **102a** is approximately equal to the distance **204** between the bottom surface of the second cladding layer **106** and the center of the tip **102a**. As a result, unnecessary material may be excluded from the second cladding layer **106** and thus a size of the semiconductor structure may be reduced.

(44) In some embodiments, a process layer **206** is disposed directly over the first cladding layer **104** and the first dielectric layer **108**. In some embodiments, the process layer **206** is a carrier layer comprising a semiconductor or some other suitable material. In some other embodiments, the process layer **206** is an adhesive layer comprising an ultraviolet (UV) curable tape or some other suitable material.

(45) FIG. 3 illustrates a cross-sectional view **300** of some embodiments of the semiconductor structure of FIG. 1A in which a top surface of the second cladding layer **106** is wider than a bottom surface of the second cladding layer **106**.

(46) For example, the second cladding layer **106** illustrated in FIG. 3 is inverted relative to the second cladding layer **106** illustrated in FIG. 1A. The second cladding layer **106** may be inverted due to the process by which the second cladding layer **106** is formed (e.g., as shown in FIGS. 28A-32A). In some other embodiments, the first cladding layer **104** and the second cladding layer **106** have substantially vertical sidewalls, as illustrated by dashed lines **302**.

(47) FIG. 4A and FIG. 4B illustrate cross-sectional views **400a**, **400b** of some embodiments of the semiconductor structure of FIG. 1A and FIG. 1B, respectively, in which a plurality of conductive interconnects **402** are disposed directly over the first cladding layer **104**, the semiconductor waveguide layer **102**, and the second cladding layer **106**.

(48) The conductive interconnects **402** are disposed within a dielectric structure **404** which comprises a plurality of dielectric layers. In some embodiments, the conductive interconnects **402** are disposed directly over the tip **102a** of the semiconductor waveguide layer **102** and other segments of the semiconductor waveguide layer **102**. The conductive interconnects **402** may, for example, include metal lines, metal vias, bond pads, contacts, or the like.

(49) In some embodiments, the conductive interconnects **402** extend through the first dielectric layer **108** to a semiconductor device layer **406** that is adjacent to the semiconductor waveguide layer **102** (e.g., adjacent to the slab device segment **102e**) and between the first dielectric layer **108** and the second dielectric layer **110**. In some embodiments, a photodetector **408** (e.g., a photodiode, an avalanche photodiode, a single photon avalanche diode, or some other suitable photodetector) is disposed within the semiconductor device layer **406**. The photodetector **408** is configured to detect optical radiation traveling through the semiconductor waveguide layer **102**. In some embodiments, some of the conductive interconnects **402** are coupled directly to the semiconductor device layer **406** and/or the photodetector **408**.

(50) FIG. 5A and FIG. 5B illustrate cross-sectional views **500a**, **500b** of some embodiments of the

semiconductor structure of FIG. 1A and FIG. 1B, respectively, in which a buffer layer 502 is directly between the semiconductor waveguide layer 102 and the first cladding layer 104.

(51) The buffer layer 502 separates the semiconductor waveguide layer 102 from the first cladding layer 104. In some embodiments, the buffer layer 502 is directly over and on opposite sides of the tip 102a and the tapered transition segment 102b, but the buffer layer 502 is not directly over nor on opposite sides of other segments (e.g., 102c, 102d, 102e) of the semiconductor waveguide layer 102. The buffer layer 502 comprises a fifth dielectric, different from the third dielectric and the fourth dielectric. In some embodiments, sidewalls of the buffer layer 502 are approximately aligned (e.g., coplanar) with sidewalls of the first cladding layer 104.

(52) The buffer layer 502 may reduce a stress put on the semiconductor waveguide layer 102 by the first cladding layer 104. For example, in some embodiments, the first cladding layer 104 comprises a harder dielectric than the first dielectric layer 108 and the buffer layer 502. Thus, the first cladding layer 104 may put stress on the semiconductor waveguide layer 102. However, by including the buffer layer 502 comprising the softer material between the semiconductor waveguide layer 102 and the first cladding layer 104, the stress put on the semiconductor waveguide layer 102 may be reduced.

(53) A thickness of the buffer layer 502 is substantially less than the thickness of the first cladding layer 104 and the thickness of the semiconductor waveguide layer 102. For example, in some embodiments, the thickness of the buffer layer 502 is less than 5% of the thickness of the first cladding layer 104, less than 2.5% of the thickness of the first cladding layer 104, or some other suitable value. Thus, the buffer layer 502 may have little impact on the mode size expansion at the tip 102a and the overall size of the semiconductor structure.

(54) In some embodiments, the buffer layer 502 may, for example, comprise silicon dioxide, silicon oxynitride, or some other suitable material. In some embodiments, the thickness of the buffer layer 502 ranges from about 5 nanometers to 30 nanometers, 10 nanometers to 25 nanometers, or some other suitable range.

(55) FIG. 6A and FIG. 6B illustrate cross-sectional views 600a, 600b of some embodiments of the semiconductor structure of FIG. 5A and FIG. 5B, respectively, in which the buffer layer 502 separates the first dielectric layer 108 from the second dielectric layer 110.

(56) In some embodiments, the buffer layer 502 also separates the first dielectric layer 108 from the semiconductor waveguide layer 102, as illustrated in FIG. 6B. For example, in some embodiments, the buffer layer 502 extends along top surfaces and sidewalls of the tapered transition segment 102b, the slab transition segment 102c, the tapered device segment 102d, and the slab device segment 102e of the semiconductor waveguide layer 102 between said segments and the first dielectric layer 108.

(57) FIG. 7A and FIG. 7B illustrate cross-sectional views 700a, 700b of some embodiments of the semiconductor structure of FIG. 5A and FIG. 5B, respectively, in which the buffer layer 502 is directly between the semiconductor waveguide layer 102 and the second cladding layer 106.

(58) The buffer layer 502 separates the semiconductor waveguide layer 102 from the second cladding layer 106. In some embodiments, the buffer layer 502 is directly under the tip 102a and the tapered transition segment 102b, but the buffer layer 502 is not directly under other segments (e.g., 102c, 102d, 102e) of the semiconductor waveguide layer 102. In some embodiments, sidewalls of the buffer layer 502 are approximately aligned (e.g., coplanar) with sidewalls of the second cladding layer 106. In some embodiments, the buffer layer 502 reduces a stress put on the semiconductor waveguide layer 102 by the second cladding layer 106.

(59) FIG. 8A and FIG. 8B illustrate cross-sectional views 800a, 800b of some embodiments of the semiconductor structure of FIG. 7A and FIG. 7B, respectively, in which the buffer layer 502 separates the first dielectric layer 108 from the second dielectric layer 110.

(60) In some embodiments, the buffer layer 502 also separates the second dielectric layer 110 from the semiconductor waveguide layer 102. For example, in some embodiments, the buffer layer 502

extends along bottom surfaces of the tapered transition segment **102b**, the slab transition segment **102c**, the tapered device segment **102d**, and the slab device segment **102e** of the semiconductor waveguide layer **102** between said segments and the second dielectric layer **110**.

(61) FIG. **9** and FIG. **10** illustrate cross-sectional views **900**, **1000** of some embodiments of the semiconductor structure of FIG. **1A** in which a first buffer layer **502a** is directly between the semiconductor waveguide layer **102** and the first cladding layer **104** and a second buffer layer **502b** is directly between the semiconductor waveguide layer **102** and the second cladding layer **106**.

(62) In some embodiments, the first buffer layer **502a** and the second buffer layer **502b** comprise a same dielectric material. In some other embodiments, the first buffer layer **502a** and the second buffer layer **502b** comprise different dielectric materials. In some embodiments, a thickness of the first buffer layer **502a** is approximately equal to a thickness of the second buffer layer **502b**.

(63) FIGS. **11A**, **12A**, **13A**, **14A**, **15A**, **16A**, **17A**, **18A**, **19A**, **20A**, **21A**, **22A**, **23A**, **24A**, **25A**, **26A**, **27A**, **28A**, **29A**, **30A**, **31A**, **32A** illustrate cross-sectional views **1100a**, **1200a**, **1300a**, **1400a**, **1500a**, **1600a**, **1700a**, **1800a**, **1900a**, **2000a**, **2100a**, **2200a**, **2300a**, **2400a**, **2500a**, **2600a**, **2700a**, **2800a**, **2900a**, **3000a**, **3100a**, **3200a** and FIGS. **11B**, **12B**, **13B**, **14B**, **15B**, **16B**, **17B**, **18B**, **19B**, **20B**, **21B**, **22B**, **23B**, **24B**, **25B**, **26B**, **27B**, **28B**, **29B**, **30B**, **31B**, **32B** illustrate corresponding three-dimensional views **1100b**, **1200b**, **1300b**, **1400b**, **1500b**, **1600b**, **1700b**, **1800b**, **1900b**, **2000b**, **2100b**, **2200b**, **2300b**, **2400b**, **2500b**, **2600b**, **2700b**, **2800b**, **2900b**, **3000b**, **3100b**, **3200b**, respectively, of some embodiments of a method for forming a semiconductor structure comprising a semiconductor waveguide layer **102**, a first cladding layer **104** along a first side **102j** of the semiconductor waveguide layer **102**, and a second cladding layer **106** along a second side **102k** of the semiconductor waveguide layer **102**. Although FIGS. **11A-32B** are described in relation to a method, it will be appreciated that the structures disclosed in FIGS. **11A-32B** are not limited to such a method, but instead may stand alone as structures independent of the method.

(64) As shown in cross-sectional view **1100a** of FIG. **11A** and corresponding three-dimensional view **1100b** of FIG. **11B**, an SOI substrate (not labeled) is provided. The SOI substrate includes a buried dielectric layer **1104** over on a semiconductor substrate layer **1102** and an upper semiconductor layer **1106** over the buried dielectric layer **1104**. In some embodiments, the buried dielectric layer has a thickness of less than about 5 micrometers or some other suitable value. In some other embodiments, the buried dielectric layer has a thickness of greater than about 5 micrometers or some other suitable value.

(65) As shown in cross-sectional view **1200a** of FIG. **12A** and corresponding three-dimensional view **1200b** of FIG. **12B**, the upper semiconductor layer (e.g., **1106** of FIGS. **11A**, **11B**) is patterned to form the semiconductor waveguide layer **102** from the upper semiconductor layer. In some embodiments, the patterning comprises forming a masking layer **1202** over the upper semiconductor layer and etching the upper semiconductor layer according to the masking layer **1202**. In some embodiments, the etching comprises a dry etching process (e.g., a plasma etching process, a reactive ion etching (RIE) process, an ion beam etching process, or some other dry etching process) or some other suitable process. In some embodiments, the masking layer **1202** comprises a photoresist layer, a hard mask layer, a combination of the foregoing, or some other suitable masking layer. In some embodiments, the masking layer **1202** is removed after and/or during the etching.

(66) As shown in cross-sectional view **1300a** of FIG. **13A** and corresponding three-dimensional view **1300b** of FIG. **13B**, in some embodiments, a first buffer layer **502a** is deposited over a first side **102j** of the semiconductor waveguide layer **102** and over the buried dielectric layer **1104**. In some embodiments, the first buffer layer **502a** may, for example, comprise silicon dioxide, silicon oxynitride, or some other suitable material and may be deposited by a chemical vapor deposition (CVD) process, a physical vapor deposition (PVD) process, an atomic layer deposition (ALD) process, or some other suitable process. In some embodiments, a thickness of the first buffer layer **502a** ranges from about 5 nanometers to 30 nanometers, 10 nanometers to 25 nanometers, or some

other suitable range. In some other embodiments, the first buffer layer **502a** is not formed over the semiconductor waveguide layer **102** and the method proceeds to FIGS. **14A**, **14B**.

(67) As shown in cross-sectional view **1400a** of FIG. **14A** and corresponding three-dimensional view **1400b** of FIG. **14B**, a first cladding layer **104** is deposited over the first side **102j** of the semiconductor waveguide layer **102**, the buried dielectric layer **1104**, and the first buffer layer **502a**. In some embodiments, the first cladding layer **104** is deposited directly on the first buffer layer **502a**. In some other embodiments, the first cladding layer **104** is deposited directly on the semiconductor waveguide layer **102** and the buried dielectric layer **1104**. The first cladding layer **104** comprises a dielectric material having a refractive index that is substantially similar to the refractive index of the semiconductor waveguide layer **102**. For example, the first cladding layer **104** may comprise silicon nitride, hafnium oxide, or some other suitable material. In some embodiments, the first cladding layer **104** may, for example, be deposited by a CVD process, a PVD process, an ALD process, or some other suitable process. In some embodiments, a thickness of the first cladding layer **104** ranges from about 2 micrometers to 5 micrometers, 3 micrometers to 5 micrometers, or some other suitable range.

(68) As shown in cross-sectional view **1500a** of FIG. **15A** and corresponding three-dimensional view **1500b** of FIG. **15B**, the first cladding layer **104** is patterned to remove the first cladding layer **104** from over segments of the semiconductor waveguide layer **102** (e.g., the slab transition segment **102c**, the tapered device segment **102d**, and the slab device segment **102e** of FIGS. **1A-1D**) not including the tip **102a** and the tapered transition segment (e.g., **102b** of FIGS. **1A-1D**). Thus, after the patterning, the tip **102a** and tapered transition segment (e.g., **102b** of FIGS. **1A-1D**) are covered by the first cladding layer **104** while the other segments (e.g., **102c**, **102d**, **102e** of FIGS. **1A-1D**) of the semiconductor waveguide layer **102** are not covered by the first cladding layer **104**. In some embodiments, the patterning comprises forming a masking layer **1502** over the first cladding layer **104** and etching the first cladding layer **104** according to the masking layer **1502**. In some embodiments, the etching comprises a dry etching process or some other suitable process. In some embodiments, the masking layer **1502** comprises a photoresist layer, a hard mask layer, a combination of the foregoing, or some other suitable masking layer. In some embodiments, the masking layer **1502** is removed after and/or during the etching.

(69) In some embodiments, the first buffer layer **502a** is also etched according to the masking layer **1502** to remove the first buffer layer **502a** from over segments of the semiconductor waveguide layer **102** (e.g., **102c**, **102d**, **102e** of FIGS. **1A-1D**) not including the tip **102a** and the tapered transition segment (e.g., **102b** of FIGS. **1A-1D**). In some embodiments, sidewalls of the first buffer layer **502a** are approximately aligned with sidewalls of the first cladding layer **104** as illustrated, for example, by dashed lines **1504** and as shown in FIGS. **5A**, **5B**.

(70) As shown in cross-sectional view **1600a** of FIG. **16A** and corresponding three-dimensional view **1600b** of FIG. **16B**, a first dielectric layer **108** is deposited over the first cladding layer **104** and the first side **102j** of the semiconductor waveguide layer **102**. In some embodiments, the first dielectric layer **108** is deposited directly on the first buffer layer **502a**. In some other embodiments, the first dielectric layer **108** is deposited directly on the buried dielectric layer **1104** and segments of the semiconductor waveguide layer **102** not covered by the first cladding layer **104**, as shown in FIGS. **1A**, **1B** and/or FIGS. **5A**, **5B**. In some embodiments, the first dielectric layer **108** may, for example, comprise silicon dioxide or some other suitable material and may be deposited by a CVD process, a PVD process, an ALD process, or some other suitable process.

(71) As shown in cross-sectional view **1700a** of FIG. **17A** and corresponding three-dimensional view **1700b** of FIG. **17B**, a planarization process is performed on the first dielectric layer **108**. In some embodiments, the planarization process comprises a chemical mechanical planarization (CMP) or some other suitable process. In some embodiments, the planarization process is also performed on the first cladding layer **104**. In some embodiments, a top surface of the first dielectric layer **108** and a top surface of the first cladding layer **104** are approximately coplanar as a result of

the planarization process. In some embodiments, the planarization process may alternatively be referred to as a polishing process or the like.

(72) As shown in cross-sectional view **1800a** of FIG. **18A** and corresponding three-dimensional view **1800b** of FIG. **18B**, in some embodiments, an interconnect structure comprising a plurality of conductive interconnects **402** is formed within a dielectric structure **404** over the first dielectric layer **108** and over the first cladding layer **104**. In some embodiments, the dielectric structure **404** is formed by depositing dielectric layers over the first dielectric layer **108** and the first cladding layer **104**. In some embodiments, the conductive interconnects **402** are formed within the dielectric structure **404** by etching the dielectric layers and subsequently depositing conductive materials over the etched dielectric layers. In some embodiments, the dielectric layers of the dielectric structure **404** may, for example, comprise silicon dioxide, silicon nitride, silicon carbide, or some other suitable material and may be deposited by one or more CVD processes, PVD processes, ALD processes, or some other suitable processes. In some embodiments, the conductive interconnects **402** may, for example, comprise copper, tungsten, aluminum, or some other suitable material and may be deposited by a CVD process, a PVD process, an ALD process, a sputtering process, or some other suitable process.

(73) As shown in cross-sectional view **1900a** of FIG. **19A** and corresponding three-dimensional view **1900b** of FIG. **19B**, a process layer **206** is formed over the first dielectric layer **108**, the first cladding layer **104**, and over the dielectric structure **404**. In some embodiments, the process layer **206** is a carrier layer comprising a semiconductor or some other material and is attached (e.g., by way of a bonding process or the like) to the dielectric structure **404** or the first dielectric layer **108**. In some other embodiments, the process layer **206** is an adhesive layer comprising a UV curable tape or some other material and is attached (e.g., by way of an adhesion process or the like) to the dielectric structure **404** or the first dielectric layer **108**.

(74) As shown in cross-sectional view **2000a** of FIG. **20A** and corresponding three-dimensional view **2000b** of FIG. **20B**, the semiconductor substrate layer (e.g., **1102** of FIGS. **19A**, **19B**) is removed from over a second side **102k** of the semiconductor waveguide layer **102** and from over the buried dielectric layer **1104** (or from under the buried dielectric layer **1104**, as shown in FIG. **20B**, depending on orientation). In some embodiments, removing the semiconductor substrate layer comprises performing a grinding process or the like on the semiconductor substrate layer. In some other embodiments, removing the semiconductor substrate layer comprises etching the semiconductor substrate layer.

(75) As shown in cross-sectional view **2100a** of FIG. **21A** and corresponding three-dimensional view **2100b** of FIG. **21B**, in some embodiments, the buried dielectric layer (e.g., **1104** of FIGS. **20A**, **20B**) is removed from over the second side **102k** of the semiconductor waveguide layer **102** (or from under the semiconductor waveguide layer **102**, as shown in FIG. **21B**, depending on orientation). In some embodiments, removing the buried dielectric layer comprises performing a grinding process or the like on the buried dielectric layer. In some other embodiments, removing the buried dielectric layer comprises etching the buried dielectric layer.

(76) In some other embodiments, the buried dielectric layer is not removed from over the second side **102k** of the semiconductor waveguide layer **102**. For example, in some embodiments where the buried dielectric layer is substantially thick (e.g., greater than or approximately equal to the thickness of the first cladding layer **104**), the buried dielectric layer is kept over the second side **102k** of the semiconductor waveguide layer **102**.

(77) As shown in cross-sectional view **2200a** of FIG. **22A** and corresponding three-dimensional view **2200b** of FIG. **22B**, in some embodiments, a second buffer layer **502b** is deposited over the second side **102k** of the semiconductor waveguide layer **102** and over the first buffer layer **502a**. In some embodiments, the second buffer layer **502b** is deposited directly on the semiconductor waveguide layer **102** and the first buffer layer **502a**. In some other embodiments, the second buffer layer **502b** is deposited directly on the semiconductor waveguide layer **102**, the first cladding layer

104, and the first dielectric layer **108**. In some embodiments, the second buffer layer **502b** may, for example, comprise silicon dioxide, silicon oxynitride, or some other suitable material and may be deposited by a CVD process, a PVD process, an ALD process, or some other suitable process. In some embodiments, a thickness of the second buffer layer **502b** ranges from about 5 nanometers to 30 nanometers, 10 nanometers to 25 nanometers, or some other suitable range. In some other embodiments, the second buffer layer **502b** is not formed over the semiconductor waveguide layer **102** and the method proceeds to FIGS. **23A**, **23B** or FIGS. **28A**, **28B**.

(78) FIGS. **23A**, **24A**, **25A**, **26A**, **27A** illustrate cross-sectional views **2300a**, **2400a**, **2500a**, **2600a**, **2700a**, and FIGS. **23B**, **24B**, **25B**, **26B**, **27B** illustrate corresponding three-dimensional views **2300b**, **2400b**, **2500b**, **2600b**, **2700b**, respectively, of some first embodiments of performing a remainder of the method for forming the semiconductor structure.

(79) As shown in cross-sectional view **2300a** of FIG. **23A** and corresponding three-dimensional view **2300b** of FIG. **23B**, in some embodiments, a second dielectric layer **110** is deposited over the second side **102k** of the semiconductor waveguide layer **102** and the second buffer layer **502b**. In some embodiments, the second dielectric layer **110** is deposited directly on the second buffer layer **502b**. In some other embodiments, the second dielectric layer **110** is deposited directly on the semiconductor waveguide layer **102** and the first buffer layer **502a**. In some other embodiments, the second dielectric layer **110** is deposited directly on the semiconductor waveguide layer **102**, the first cladding layer **104**, and the first dielectric layer **108**. In some embodiments, the second dielectric layer **110** may, for example, comprise silicon dioxide or some other suitable material and may be deposited by a CVD process, a PVD process, an ALD process, or some other suitable process.

(80) In some embodiments where the buried dielectric layer (e.g., **1104** of FIGS. **20A**, **20B**) is kept over the second side **102k** of the semiconductor waveguide layer **102**, the second dielectric layer **110** may not be deposited and the method proceeds to FIGS. **24A**, **24B**.

(81) As shown in cross-sectional view **2400a** of FIG. **24A** and corresponding three-dimensional view **2400b** of FIG. **24B**, the second dielectric layer **110** is etched to form a cavity **2404** in the second dielectric layer **110**. In some embodiments, a masking layer **2402** is formed over the second dielectric layer **110** and the second dielectric layer **110** is etched according to the masking layer **2402** to form the cavity **2404**. The cavity **2404** is formed directly over the tip **102a** and the tapered transition segment (e.g., **102b** of FIGS. **1A-1D**) but not over other segments (e.g., the slab transition segment **102c**, the tapered device segment **102d**, and the slab device segment **102e** of FIGS. **1A-1D**) of the semiconductor waveguide layer **102**. In some embodiments, the etching comprises a dry etching process or some other suitable process. In some embodiments, the masking layer **2402** comprises a photoresist layer, a hard mask layer, a combination of the foregoing, or some other suitable masking layer. In some embodiments, the masking layer **2402** is removed after and/or during the etching.

(82) In some embodiments where the buried dielectric layer (e.g., **1104** of FIGS. **20A**, **20B**) is kept over the second side **102k** of the semiconductor waveguide layer **102**, the buried dielectric layer is etched (instead of the second dielectric layer **110**) to form the cavity **2404** in buried dielectric layer.

(83) As shown in cross-sectional view **2500a** of FIG. **25A** and corresponding three-dimensional view **2500b** of FIG. **25B**, a second cladding layer **106** is deposited over the second dielectric layer **110** and in the cavity (e.g., **2404** of FIGS. **24A**, **24B**). The second cladding layer **106** fills the cavity in the second dielectric layer **110**. In some embodiments, the second cladding layer **106** is deposited directly on the second buffer layer **502b**. In some other embodiments, the second cladding layer **106** is deposited directly on the semiconductor waveguide layer **102** and the first buffer layer **502a**. In some other embodiments, the second cladding layer **106** is deposited directly on the semiconductor waveguide layer **102** and the first cladding layer **104**.

(84) The second cladding layer **106** comprises a dielectric material having a refractive index that is substantially similar to the refractive index of the semiconductor waveguide layer **102**. For

example, in some embodiments, the second cladding layer **106** comprises silicon nitride, hafnium oxide, or some other suitable material. In some embodiments, the second cladding layer **106** may, for example, be deposited by a CVD process, a PVD process, an ALD process, or some other suitable process. In some embodiments, a thickness of the second cladding layer **106** ranges from about 2 micrometers to 5 micrometers, 3 micrometers to 5 micrometers, or some other suitable range.

(85) In some embodiments where the buried dielectric layer (e.g., **1104** of FIGS. **20A**, **20B**) is kept over the second side **102k** of the semiconductor waveguide layer **102**, the second cladding layer **106** is deposited over the buried dielectric layer and in the cavity in the buried dielectric layer.

(86) As shown in cross-sectional view **2600a** of FIG. **26A** and corresponding three-dimensional view **2600b** of FIG. **26B**, a planarization process is performed on the second cladding layer **106**. In some embodiments, the planarization process comprises a CMP or some other suitable process. In some embodiments, the planarization process is also performed on the second dielectric layer **110** or the buried dielectric layer. In some embodiments, a top surface of the second cladding layer **106** and a top surface of the second dielectric layer **110** are approximately coplanar as a result of the planarization process.

(87) As shown in cross-sectional view **2700a** of FIG. **27A** and corresponding three-dimensional view **2700b** of FIG. **27B**, an optical fiber **112** is optically coupled to the semiconductor waveguide layer **102**. In some embodiments, a diameter of the optical fiber **112** (e.g., the diameter of the core of the optical fiber **112**) ranges from about 8 micrometers to 10 micrometers or some other suitable range.

(88) FIGS. **28A**, **29A**, **30A**, **31A**, **32A** illustrate cross-sectional views **2800a**, **2900a**, **3000a**, **3100a**, **3200a**, and FIGS. **28B**, **29B**, **30B**, **31B**, **32B** illustrate corresponding three-dimensional views **2800b**, **2900b**, **3000b**, **3100b**, **3200b**, respectively, of some second embodiments of performing a remainder of the method for forming the semiconductor structure.

(89) As shown in cross-sectional view **2800a** of FIG. **28A** and corresponding three-dimensional view **2800b** of FIG. **28B**, the second cladding layer **106** is deposited over the second side **102k** of the semiconductor waveguide layer **102** and over the second buffer layer **502b**. In some embodiments, the second cladding layer **106** is deposited directly on the second buffer layer **502b**. In some other embodiments, the second cladding layer **106** is deposited directly on the semiconductor waveguide layer **102** and the first buffer layer **502a**. In some other embodiments, the second cladding layer **106** is deposited directly on the semiconductor waveguide layer **102**, the first cladding layer **104**, and the first dielectric layer **108**.

(90) As shown in cross-sectional view **2900a** of FIG. **29A** and corresponding three-dimensional view **2900b** of FIG. **29B**, the second cladding layer is patterned to remove the second cladding layer **106** from over segments of the semiconductor waveguide layer **102** (e.g., the slab transition segment **102c**, the tapered device segment **102d**, and the slab device segment **102e** of FIGS. **1A-1D**) not including the tip **102a** and the tapered transition segment (e.g., **102b** of FIGS. **1A-1D**). Thus, after the patterning, the tip **102a** and the tapered transition segment are covered by the second cladding layer **106** while the other segments of the semiconductor waveguide layer **102** are not covered by the second cladding layer **106**. In some embodiments, the patterning comprises forming a masking layer **2902** over the second cladding layer **106** and etching the second cladding layer **106** according to the masking layer **2902**. In some embodiments, the etching comprises a dry etching process or some other suitable process. In some embodiments, the masking layer **2902** comprises a photoresist layer, a hard mask layer, a combination of the foregoing, or some other suitable masking layer. In some embodiments, the masking layer **2902** is removed after and/or during the etching.

(91) In some embodiments, the second buffer layer **502b** is also etched according to the masking layer **2902** to remove the second buffer layer **502b** from over segments of the semiconductor waveguide layer **102** (e.g., the slab transition segment **102c**, the tapered device segment **102d**, and

the slab device segment **102e** of FIGS. **1A-1D**) not including the tip **102a** and the tapered transition segment (e.g., **102b** of FIGS. **1A-1D**). In some such embodiments, sidewalls of the second buffer layer **502b** are approximately aligned with sidewalls of the second cladding layer **106** as illustrated, for example, by dashed lines **2904** and as shown in FIGS. **7A, 7B**.

(92) As shown in cross-sectional view **3000a** of FIG. **30A** and corresponding three-dimensional view **3000b** of FIG. **30B**, the second dielectric layer **110** is deposited over the second cladding layer **106** and over the second buffer layer **502b**. In some embodiments, the second dielectric layer **110** is deposited directly on the second cladding layer **106** and the second buffer layer **502b**. In some other embodiments, the second dielectric layer **110** is deposited directly on the second cladding layer **106** and the first buffer layer **502a**. In some other embodiments, the second dielectric layer **110** is deposited directly on the second cladding layer **106** and the first dielectric layer **108**.

(93) As shown in cross-sectional view **3100a** of FIG. **31A** and corresponding three-dimensional view **3100b** of FIG. **31B**, a planarization process is performed on the second dielectric layer **110**. In some embodiments, the planarization process comprises a CMP or some other suitable process. In some embodiments, the planarization process is also performed on the second cladding layer **106**. In some embodiments, a top surface of the second dielectric layer **110** and a top surface of the second cladding layer **106** are approximately coplanar as a result of the planarization process.

(94) As shown in cross-sectional view **3200a** of FIG. **32A** and corresponding three-dimensional view **3200b** of FIG. **32B**, an optical fiber **112** is optically coupled to the semiconductor waveguide layer **102**.

(95) FIG. **33** illustrates a flow diagram of some embodiments of a method **3300** for forming a semiconductor structure comprising a semiconductor waveguide layer, a first cladding layer along a first side of the semiconductor waveguide layer, and a second cladding layer along a second side of the semiconductor waveguide layer. While method **3300** is illustrated and described below as a series of acts or events, it will be appreciated that the illustrated ordering of such acts or events are not to be interpreted in a limiting sense. For example, some acts may occur in different orders and/or concurrently with other acts or events apart from those illustrated and/or described herein. In addition, not all illustrated acts may be required to implement one or more aspects or embodiments of the description herein. Further, one or more of the acts depicted herein may be carried out in one or more separate acts and/or phases.

(96) At block **3302**, form a semiconductor waveguide layer over a substrate. FIG. **12A** illustrates a cross-sectional view **1200a** of some embodiments corresponding to block **3302**.

(97) At block **3304**, deposit a first cladding layer over a first side of the semiconductor waveguide layer. FIG. **14A** illustrates a cross-sectional view **1400a** of some embodiments corresponding to block **3304**.

(98) At block **3306**, remove the first cladding layer from over segments of the semiconductor waveguide layer not including a tip of the semiconductor waveguide layer. FIG. **15A** illustrates a cross-sectional view **1500a** of some embodiments corresponding to block **3306**.

(99) At block **3308**, deposit a first dielectric layer over the first cladding layer and over the first side of the semiconductor waveguide layer. FIG. **16A** illustrates a cross-sectional view **1600a** of some embodiments corresponding to block **3308**.

(100) At block **3310**, form a second cladding layer and a second dielectric layer over a second side of the semiconductor waveguide layer, where the second cladding layer is formed over the tip of the semiconductor waveguide layer. FIGS. **23A, 24A, 25A** illustrate cross-sectional views **2300a, 2400a, 2500a**, respectively, of some embodiments corresponding to block **3310**. FIGS. **28A, 29A, 30A** illustrate cross-sectional views **2800a, 2900a, 3000a**, respectively, of some other embodiments corresponding to block **3310**. In some embodiments, block **3310** includes blocks **3312a, 3314a, 3316a**. In some other embodiments, block **3310** includes blocks **3312b, 3314b, 3316b**.

(101) At block **3312a**, deposit a second dielectric layer over the second side of the semiconductor

waveguide layer. FIG. 23A illustrates a cross-sectional view **2300a** of some embodiments corresponding to block **3312a**.

(102) At block **3314a**, form a cavity in the second dielectric layer directly over the tip of the semiconductor waveguide layer. FIG. 24A illustrates a cross-sectional view **2400a** of some embodiments corresponding to block **3314a**.

(103) At block **3316a**, deposit a second cladding layer in the cavity and over the tip of the semiconductor waveguide layer. FIG. 25A illustrates a cross-sectional view **2500a** of some embodiments corresponding to block **3316a**.

(104) At block **3312b**, deposit a second cladding layer over the second side of the semiconductor waveguide layer. FIG. 28A illustrates a cross-sectional view **2800a** of some embodiments corresponding to block **3312b**.

(105) At block **3314b**, remove the second cladding layer from over segments of the semiconductor waveguide layer not including the tip of the semiconductor waveguide layer. FIG. 29A illustrates a cross-sectional view **2900a** of some embodiments corresponding to block **3314b**.

(106) At block **3316b**, deposit a second dielectric layer over the second cladding layer and over the second side of the semiconductor waveguide layer. FIG. 30A illustrates a cross-sectional view **3000a** of some embodiments corresponding to block **3316b**.

(107) Thus, the present disclosure relates to a semiconductor structure comprising a semiconductor waveguide layer which tapers to a tip, where the tip is surrounded by a first cladding layer and a second cladding layer to improve a performance of the semiconductor structure.

(108) Accordingly, in some embodiments, the present disclosure relates to a semiconductor structure including a first dielectric layer and a second dielectric layer under the first dielectric layer. A semiconductor waveguide layer is over the second dielectric layer and between first sidewalls of the first dielectric layer. A first cladding layer is between the first sidewalls of the first dielectric layer and directly over the semiconductor waveguide layer. A second cladding layer is between first sidewalls of the second dielectric layer and directly under the semiconductor waveguide layer. A difference between a refractive index of the semiconductor waveguide layer and a refractive index of the first cladding layer is less than a difference between the refractive index of the semiconductor waveguide layer and a refractive index of the first dielectric layer. A difference between the refractive index of the semiconductor waveguide layer and a refractive index of the second cladding layer is less than a difference between the refractive index of the semiconductor waveguide layer and a refractive index of the second dielectric layer.

(109) In other embodiments, the present disclosure relates to a semiconductor structure including a first dielectric layer, a second dielectric layer, a semiconductor waveguide layer, a first cladding layer, and a second cladding layer. The first dielectric layer includes a first dielectric having a first refractive index. The second dielectric layer is under the first dielectric layer and includes a second dielectric having a second refractive index. The semiconductor waveguide layer is over the second dielectric layer and between sidewalls of the first dielectric layer. The semiconductor waveguide layer includes a first segment and a second segment. A width of the first segment is tapered along a length of the first segment to a tip. The semiconductor waveguide layer has a third refractive index. A first cladding layer is between the sidewalls of the first dielectric layer, on opposite sides of the first segment and the tip, and directly over the first segment and the tip. The first cladding layer includes a third dielectric having a fourth refractive index. The second cladding layer is between sidewalls of the second dielectric layer and directly under the first segment and the tip. The second cladding layer includes the third dielectric having the fourth refractive index. A difference between the third refractive index and the fourth refractive index is less than a difference between the third refractive index and the first refractive index and less than a difference between the third refractive index and the second refractive index.

(110) In yet other embodiments, the present disclosure relates to a method for forming a semiconductor structure. The method includes depositing a first cladding layer over a first side of a

semiconductor waveguide layer. The semiconductor waveguide layer includes a tapered segment between a device segment and a tip of the semiconductor waveguide layer. The first cladding layer is etched to remove the first cladding layer from over the device segment. The first cladding layer remains over the tip and the tapered segment after the etching. A first dielectric layer is deposited over the first cladding layer and over the first side of the semiconductor waveguide layer. A second dielectric layer is deposited over a second side of the semiconductor waveguide layer, opposite the first side. A second cladding layer is formed over the second side of the semiconductor waveguide layer and directly over the first cladding layer, the tip, and the tapered segment. A difference between a refractive index of the semiconductor waveguide layer and a refractive index of the first cladding layer is less than a difference between the refractive index of the semiconductor waveguide layer and a refractive index of the first dielectric layer. A difference between the refractive index of the semiconductor waveguide layer and a refractive index of the second cladding layer is less than a difference between the refractive index of the semiconductor waveguide layer and a refractive index of the second dielectric layer.

(111) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A method for forming a semiconductor structure, the method comprising: depositing a first cladding layer along a first side of a semiconductor waveguide layer and over a device segment, a tapered segment, and a tip of the semiconductor waveguide layer, wherein tapered segment is between the device segment and the tip of the semiconductor waveguide layer; etching the first cladding layer to remove the first cladding layer from over the device segment, wherein the first cladding layer remains over the tip and the tapered segment after the etching of the first cladding layer; depositing a first dielectric layer over the first cladding layer and along the first side of the semiconductor waveguide layer; depositing a second dielectric layer along a second side of the semiconductor waveguide layer, opposite the first side, and over the device segment, the tapered segment, the first cladding layer, and the first dielectric layer; and depositing a second cladding layer along the second side of the semiconductor waveguide layer, beside the second dielectric layer, and over the first cladding layer, the tip, and the tapered segment, wherein a difference between a refractive index of the semiconductor waveguide layer and a refractive index of the first cladding layer is less than a difference between the refractive index of the semiconductor waveguide layer and a refractive index of the first dielectric layer.
2. The method of claim 1, wherein the second dielectric layer is deposited over the tip, the method further comprising: etching the second dielectric layer to form a cavity in the second dielectric layer directly over the tip and the tapered segment, wherein the second cladding layer is deposited in the cavity, wherein a difference between the refractive index of the semiconductor waveguide layer and a refractive index of the second cladding layer is less than a difference between the refractive index of the semiconductor waveguide layer and a refractive index of the second dielectric layer.
3. The method of claim 1, further comprising: depositing a first buffer layer over the first side of the semiconductor waveguide layer before the first cladding layer is deposited over the first side of the semiconductor waveguide layer, wherein the first cladding layer is deposited over the first

buffer layer.

4. The method of claim 1, further comprising: removing a semiconductor substrate layer and a buried dielectric layer from a second side of the semiconductor waveguide layer, opposite the first side, wherein the second dielectric layer is deposited along the second side of the semiconductor waveguide layer in place of the buried dielectric layer.

5. The method of claim 1, further comprising: forming an interconnect structure over the first dielectric layer and the first cladding layer.

6. The method of claim 5, further comprising: forming a process layer over the interconnect structure.

7. The method of claim 1, wherein the first cladding layer and the second cladding layer comprise a first dielectric material, and wherein the first dielectric layer comprises a second dielectric material different than the first dielectric material.

8. The method of claim 1, wherein the semiconductor waveguide layer comprises silicon and the first cladding layer comprises silicon nitride.

9. A method for forming a semiconductor structure, the method comprising: etching a semiconductor layer to form a semiconductor waveguide having a tapered segment, a device segment, and a tip, wherein the tapered segment is laterally between the device segment and the tip; depositing a first cladding layer comprising a first dielectric material over the tapered segment, the device segment, and the tip of the semiconductor waveguide; etching the first cladding layer to remove the first cladding layer from over the device segment and from over a first portion of the tapered segment, wherein the first cladding layer remains over the tip and a second portion of the tapered segment after the first cladding layer is etched; depositing a first dielectric layer comprising a second dielectric material, different than the first dielectric material, over the first cladding layer, the first portion of the tapered segment, and the device segment after etching the first cladding layer; depositing a second dielectric layer comprising a third dielectric material, different than the first dielectric material, under the first dielectric layer, the first cladding layer, the tip, the tapered segment, and the device segment; etching the second dielectric layer to remove a first portion of the second dielectric layer from under the first cladding layer, the tip, and the second portion of the tapered segment to expose the tip and the second portion of the tapered segment, wherein a second portion of the second dielectric layer remains under the first cladding layer, the first dielectric layer, the device segment, and the first portion of the tapered segment after the etching of the second dielectric layer; and depositing a second cladding layer comprising the first dielectric material under the tip and the second portion of the tapered segment in place of the first portion of the second dielectric layer.

10. The method of claim 9, wherein the semiconductor layer is over a buried dielectric layer, and wherein the buried dielectric layer is over a semiconductor substrate, the method further comprising: removing the semiconductor substrate from under the buried dielectric layer; removing the buried dielectric layer from under the semiconductor layer; and depositing the second dielectric layer under the semiconductor layer.

11. The method of claim 9, further comprising: depositing a first buffer layer over the tapered segment, the device segment, and the tip of the semiconductor waveguide before the first cladding layer is deposited over the tapered segment, the device segment, and the tip of the semiconductor waveguide, wherein the first cladding layer is deposited over the first buffer layer.

12. The method of claim 11, wherein the first buffer layer comprises a fourth dielectric material different than the first dielectric material.

13. The method of claim 11, wherein a thickness of the first buffer layer is substantially less than a thickness of the first cladding layer and a thickness of the semiconductor layer.

14. The method of claim 9, wherein the second cladding layer is deposited directly on a bottom of the tip and a bottom of the second portion of the tapered segment.

15. A method for forming a semiconductor structure, the method comprising: etching a

semiconductor layer having a first refractive index to form a semiconductor waveguide having a tapered segment, a device segment, and a tip, wherein the tapered segment is laterally between the device segment and the tip, wherein the semiconductor waveguide is over a buried dielectric layer; depositing a first cladding layer having a second refractive index over the tapered segment, the device segment, and the tip of the semiconductor waveguide; etching the first cladding layer to remove the first cladding layer from over the device segment and from over a first portion of the tapered segment, wherein the first cladding layer remains over the tip and a second portion of the tapered segment after the first cladding layer is etched; depositing a first dielectric layer having a third refractive index over the first cladding layer, the first portion of the tapered segment, and the device segment; removing the buried dielectric layer from under the semiconductor layer; depositing a second dielectric layer under the semiconductor layer in place of the buried dielectric layer, wherein the second dielectric layer has a fourth refractive index and is deposited under the first portion of the tapered segment, under the device segment, and beside the second cladding layer; and forming a second cladding layer having the second refractive index under the tip and the second portion of the tapered segment, wherein the second refractive index is less than the first refractive index, greater than the third refractive index, and greater than the fourth refractive index.

16. The method of claim 15, further comprising: depositing a buffer layer having a fifth refractive index over the semiconductor waveguide before the first cladding layer is deposited, wherein the first cladding layer is deposited over the buffer layer, and wherein the fifth refractive index is less than the second refractive index.

17. The method of claim 15, wherein the second dielectric layer is deposited under the tip, the method further comprising: etching the second dielectric layer to remove the second dielectric layer from under the tip and the second portion of the tapered segment, wherein the second cladding layer is formed by depositing the second cladding layer beside the second dielectric layer, under the tip, and under the second portion of the tapered segment after the second dielectric layer is etched.

18. The method of claim 15, wherein the second dielectric layer is deposited under the first dielectric layer.

19. The method of claim 15, further comprising: removing a semiconductor substrate from under the buried dielectric layer before removing the buried dielectric layer from under the semiconductor layer.

20. The method of claim 15, wherein the fourth refractive index is approximately equal to the third refractive index.
