

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent

12408425

Kind Code

B2

Date of Patent

September 02, 2025

Inventor(s)

Lin; Ta-Chun et al.

Semiconductor structure with high integration density and method for manufacturing the same

Abstract

A semiconductor structure includes: a substrate; a first fin and a second fin disposed on the substrate and spaced apart from each other; a dielectric wall disposed on the substrate and having first and second wall surfaces; a third fin disposed on the substrate to be in direct contact with at least one of the first and second fins; a first device disposed on the first fin and including first channel features extending away from the first wall surface; a second device disposed on the second fin and including second channel features extending away from the second wall surface; at least one third device disposed on the third fin and including third channel features; and an isolation feature disposed on the substrate to permit the third device to be electrically isolated from the first and second devices. A method for manufacturing the semiconductor structure is also disclosed.

Inventors: Lin; Ta-Chun (Hsinchu, TW), Tsai; Ming-Heng (Hsinchu, TW), Chang; Huang-Chao (Hsinchu, TW), Liang; Chun-Sheng (Hsinchu, TW), Chang; Chih-Hao (Hsinchu, TW), Liaw; Jhon Jhy (Hsinchu, TW)

Applicant: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.
(Hsinchu, TW)

Family ID: 90141750

Assignee: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.
(Hsinchu, TW)

Appl. No.: 18/169628

Filed: February 15, 2023

Prior Publication Data

Document Identifier

US 20240088149 A1

Publication Date

Mar. 14, 2024

Related U.S. Application Data

us-provisional-application US 63405988 20220913

Publication Classification

Int. Cl.: H10D84/85 (20250101); H10D30/01 (20250101); H10D30/43 (20250101); H10D30/67 (20250101); H10D62/10 (20250101); H10D62/13 (20250101); H10D64/01 (20250101); H10D84/01 (20250101); H10D84/03 (20250101)

U.S. Cl.:

CPC H10D84/85 (20250101); H10D30/014 (20250101); H10D30/43 (20250101); H10D30/6735 (20250101); H10D62/121 (20250101); H10D62/151 (20250101); H10D64/017 (20250101); H10D84/0167 (20250101); H10D84/017 (20250101); H10D84/0188 (20250101); H10D84/038 (20250101);

Field of Classification Search

CPC: H10D (84/85); H10D (84/0167); H10D (84/017); H10D (84/0188); H10D (84/038); H10D (84/0151); H10D (84/83); H10D (30/014); H10D (30/43); H10D (30/6735); H10D (30/6757); H10D (62/121); H10D (62/151); H10D (64/017)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
10879351	12/2019	Ching	N/A	H10D 84/0135
12107006	12/2023	You	N/A	H10D 30/031
2019/0305082	12/2018	Ching	N/A	H10D 84/0158
2021/0098471	12/2020	Chen	N/A	H01L 21/76877
2022/0130955	12/2021	Cheng	N/A	H10D 84/0158
2022/0359711	12/2021	Lu	N/A	H10D 84/0188
2024/0120377	12/2023	Lin	N/A	H10D 84/83

Primary Examiner: Nguyen; Dao H

Attorney, Agent or Firm: Cooper Legal Group, LLC

Background/Summary

REFERENCE TO RELATED APPLICATION (1) This application claims priority of U.S. Provisional Patent Application No. 63/405,988, filed on Sep. 13, 2022, the contents of which is incorporated herein by reference in its entirety.

BACKGROUND

(1) Transistors are key active components in modern integrated circuits (ICs). With rapid development of semiconductor technology, critical dimension (CD) of transistors keeps shrinking

and various three-dimensional (3D) transistor structures are springing up, making it possible to integrate a large number of transistors per unit area. In addition, transistors in an IC may not be exactly the same, and may have difference in configuration and/or size, so that the transistors can be integrated together to form different operating units (e.g., memories, inverters, logic gates, flash, etc.) with different functions. Till date, advanced node 3D ICs including different operating units integrated therein are under continuous development.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.
- (2) FIG. 1 is a flow diagram illustrating a method for manufacturing a semiconductor structure in accordance with some embodiments.
- (3) FIGS. 2 to 32 illustrate schematic views of intermediate stages of the method depicted in FIG. 1 in accordance with some embodiments.
- (4) FIGS. 33 to 36 are schematic views respectively illustrating first to fourth device layouts in accordance with some embodiments.

DETAILED DESCRIPTION

- (5) The following disclosure provides many different embodiments, or examples, for implementing different features of the disclosure. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.
- (6) Further, spatially relative terms, such as “on,” “above,” “top,” “bottom,” “upper,” “lower,” “over,” “beneath,” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.
- (7) Although critical dimension (CD) of transistors continues to shrink and various three-dimensional (3D) transistor structures (e.g., a gate-all-around (GAA) structure, a forksheet structure, etc.) are springing up for manufacturing integrated circuit (IC) with a high integration density, some transistors that are designed for high-speed computing require a channel having a relatively large channel width in a Y direction (see FIG. 2). In general, a forksheet-dominant device layout has an integration density that is greater than that of a GAA-dominant device layout due to a relatively smaller channel width in the Y direction. In a forksheet-dominant device layout in which any two of transistors are integrated by a forksheet structure, a dielectric wall is provided to be interposed between the two transistors for isolation. The two transistors and the dielectric wall have a total width in the Y direction with a certain value so as to permit the transistors to be periodically and densely arranged in the forksheet-dominant device layout. Since the dielectric wall has a

minimum width in the Y direction, there is a physical limit when a channel of any one(s) of the two transistors is required to be enlarged in the Y direction for high-speed computing requirements. Therefore, the present disclosure provides a solution for integrating a GAA-dominant device layout into a forksheet-dominant device layout so as to integrate different operating units (e.g., memories, inverters, logic gates, flash, etc.) with different operational requirement (e.g., low power consumption, high-speed computing, etc.) in one IC. In the following, the present disclosure is directed to a semiconductor structure including a plurality of devices adjacent to each other and having various channel widths. The devices in the semiconductor structure may be independently configured as nanosheet gate-all-around field-effect transistors (GAA FETs), nanowire GAA FETs, complementary FETs (CFET), fork-sheet FETs, or other suitable configurations. The devices in the semiconductor structure may be integrated to function as memory cells, inverters, logic gates (e.g., NOR gates and NAND gates), or other suitable applications.

(8) FIG. 1 is flow diagram illustrating a method **100** for manufacturing a semiconductor structure (for example, a semiconductor structure **90** shown in FIG. 30) in accordance with some embodiments. FIGS. 2 to 32 illustrate schematic views of intermediate stages of the method **100** in accordance with some embodiments. Some repeating structures are omitted in FIGS. 2 to 32 for the sake of brevity.

(9) Referring to FIG. 1 and the examples illustrated in FIGS. 2, 3 and 4, the method **100** begins at step **101**, where a patterned structure is formed. FIG. 2 is a top schematic view of the patterned structure in accordance with some embodiment, in which fins **11**, **12**, **13** are shown and other elements are omitted. FIGS. 3 and 4 are cross-sectional views respectively taken along lines A-A' and B-B' of FIG. 2 in accordance with some embodiments, but further illustrating the other elements omitted in FIG. 2.

(10) The patterned structure includes a substrate **10**, a plurality pairs of fins (each pair of which includes a first fin **11** and a second fin **12**) disposed on the substrate **10**, at least one third fin **13** disposed on the substrate **10**, a plurality pairs of stacks (each pair of which includes a first stack **14** disposed on the first fin **11** of a corresponding pair of the fins, and a second stack **15** disposed on the second fin **12** of a corresponding pair of the fins), at least one third stack **16** disposed on the at least one third fin **13**, and a plurality of isolation regions **17** disposed among the first, second, and third fins **11**, **12**, **13**. In each pair of the fins **11**, **12**, the first and second fins **11**, **12** are each elongated in an X direction transverse to the Y direction, and are spaced apart from each other in the Y direction. The at least one third fin **13** is elongated in the X direction and is in direct contact with at least one of the first and second fins **11**, **12**.

(11) In some embodiments, as shown in FIG. 2, the patterned structure includes two pairs of the fins **11**, **12** (i.e., a first pair **1A** and a second pair **1B**), two pairs of the stacks **14**, **15**, three of the third fins **13** (i.e., a main fin **130**, a first auxiliary fin **131** and a second auxiliary fin **132**) and three of the third stacks **16**. The first and second auxiliary fins **131**, **132** are located at opposite sides of the main fin **130** in the Y direction, and each of the first and second auxiliary fins **131**, **132** is spaced apart from the main fin **130** in the Y direction. The second fin **12** of the first pair **1A** is disposed to confront the first fin **11** of the second pair **1B** in the Y direction. The main fin **130** is in direct contact with the second fin **12** of the first pair **1A** and the first fin **11** of the second pair **1B**. The first auxiliary fin **131** is in direct contact with the first fin **11** of the first pair **1A**. The second auxiliary fin **132** is in direct contact with the second fin **12** of the second pair **1B**.

(12) Each of the fins **11**, **12**, **13** has a fin width in the Y direction. In some embodiments, at least one of the third fins **13** has a fin width (FW20, FW21, FW22) that is greater than a fin width (FW11, FW12) of each of the first and second fins **11**, **12**. In some embodiments, fin widths (FW20, FW21, FW22) of the third fins **13** may be different from each other. For example, the main fin **130** may have a fin width (FW20) that is greater than a fin width (FW21, FW22) of each of the first and second auxiliary fins **131**, **132**. In some embodiments, in each pair of the fins **11**, **12**, the first fin **11** may have a fin width (FW11) the same as a fin width (FW12) of the second fin **12**. In

some other embodiments, in each pair of the fins **11**, **12**, the first fin **11** may have a fin width (FW**11**) different from a fin width (FW**12**) of the second fin **12**, as shown in FIG. 2.

(13) In some embodiments, as shown in FIGS. 3 and 4, each of the stacks **14**, **15**, **16** has a stack width (SW**11**, SW**12**, SW**20**, SW**21**, SW**22**) in the Y direction substantially equal to a fin width of a corresponding one of the fins **11**, **12**, **13** disposed therebeneath. The stack widths (SW**11**, SW**12**, SW**20**, SW**21**, SW**22**) of the stacks **14**, **15**, **16**, which are adjustable and determined in step **101**, will respectively affect channel widths (CW**11**, CW**12**, CW**20**, CW**21**, CW**22**) in the Y direction of channel features **182A** (see FIGS. 13 and 14) to be subsequently formed.

(14) FIG. 5 is a view similar to that of FIG. 2 but illustrating a different relationship among the first, second and third fins **11**, **12**, **13** in accordance with some other embodiments. As shown in FIG. 5, the patterned structure includes a single pair of the fins (i.e., the first fin **11** and the second fin **12**) and a single third fin **13** in direct contact with both the first and second fins **12**.

(15) In some embodiments, the substrate **10** may be made of elemental semiconductor materials, such as crystalline silicon (Si), diamond, or germanium (Ge); compound semiconductor materials, such as gallium nitride (GaN), silicon carbide (SiC), gallium arsenide (GaAs), indium arsenide (InAs), or indium phosphide (InP); or alloy semiconductor materials, such as silicon germanium (SiGe), silicon germanium carbide, gallium arsenic phosphide (GaAsP), or gallium indium phosphide (GaInP). The material for forming the substrate **10** may be doped with p-type impurities or n-type impurities, or undoped. In addition, the substrate **10** may be a bulk silicon substrate, a silicon-on-insulator (SOI) substrate, or a germanium-on-insulator (GOI) substrate. Other suitable materials and/or configurations for the substrate **10** are within the contemplated scope of the present disclosure.

(16) Each of the fins **11**, **12**, **13** may be independently made of a material the same as or different from that of the substrate **10** as described above. The material for forming the fins **11**, **12**, **13** may be doped with p-type impurities or n-type impurities, or undoped. In some embodiments, when one of the fins **11**, **12**, **13** is designed for forming an n-FET thereon, the one of the fins **11**, **12**, **13** may be doped with p-type impurities; and when one of the fins **11**, **12**, **13** is designed for forming a p-FET thereon, the one of the fins **11**, **12**, **13** may be doped with n-type impurities so as to reduce a substrate leakage current.

(17) Each of the stacks **14**, **15**, **16** includes a plurality of sacrificial layers **181** and a plurality of channel layers **182** disposed to alternate with the sacrificial layers **181** in a Z direction transverse to both the X and Y directions. In some embodiments, the X, Y, and Z directions are perpendicular to one another. In some embodiments, an uppermost one of the channel layers **182** is disposed over an uppermost one of the sacrificial layers **181**. The number of the sacrificial layers **181** and the channel layers **182** in each of the first, second and third stacks **14**, **15**, **16** are determined according to application requirements. In some embodiments, each of the stacks **14**, **15**, **16** further includes a mask layer **183** disposed on the uppermost one of the channel layers **182**. In FIGS. 3 and 4, in each of the stacks **14**, **15**, **16**, the number of each of the sacrificial layers **181** and the channel layers **182** is three. Although FIGS. 3 and 4 show that the thickness of each of the sacrificial layers **181** is greater than that of each of the channel layers **182**, the thickness of each of the sacrificial layers **181** may be equal to or smaller than that of each of the channel layers **182** according to practical requirements.

(18) Suitable materials for the sacrificial layers **181** and the channel layers **182** are similar to those for the substrate **10**, but the material of the sacrificial layers **181** is different from that of the channel layers **182**, so that the sacrificial layers **181** can be selectively removed with respect to the material of the channel layers **182** during subsequent processes. In some embodiments, each of the channel layers **182** is made of Si, and each of the sacrificial layers **181** is made of SiGe. Other suitable materials for the sacrificial layers **181** and the channel layers **182** are within the contemplated scope of the present disclosure. The mask layer **183** may include a low dielectric constant (low-k) material (such as silicon oxide, silicon nitride, silicon oxynitride, silicon

carbonitride, silicon oxycarbide, silicon oxycarbonitride, silicon carbide, and so on), a high dielectric constant (high-k) material (such as hafnium oxide, zirconium oxide, zirconium aluminum oxide, hafnium aluminum oxide, hafnium silicon oxide, aluminum oxide, and so on), or a combination thereof. Other suitable materials for the mask layer **183** are within the contemplated scope of the present disclosure.

(19) In some embodiments, each of the isolation regions **17** may be a portion of a shallow trench isolation (STI), a deep trench isolation (DTI), or other suitable structures. The isolation regions **17** may include a suitable low-k material (such as the examples described in the preceding paragraph). Other suitable materials and/or configurations for the isolation regions **17** are within the contemplated scope of the present disclosure.

(20) In some embodiments, the patterned structure may be formed by (i) patterning a semiconductor substrate and a stack unit (not shown) formed thereon to form the fins **11**, **12**, **13** on the substrate **10** and the stacks **14**, **15**, **16** respectively on the fins **11**, **12**, **13** (the semiconductor substrate is patterned into the substrate **10** and the fins **11**, **12**, **13**, and the stack unit is patterned into the stacks **14**, **15**, **16**), (ii) forming an isolation layer to cover the substrate **10** and the stacks **14**, **15**, **16**, followed by a planarization process, for example, but not limited to, chemical mechanism polishing (CMP), to form isolation portions among the stacks **14**, **15**, **16**, and (iii) recessing the isolation portions to form the isolation regions **17** by dry etching so as to expose the stacks **14**, **15**, **16**. Other suitable processes for forming the patterned structure are within the contemplated scope of the present disclosure.

(21) Referring to FIG. **1** and the examples illustrated in FIGS. **8**, **9**, and **10**, the method **100** proceeds to step **102**, where a plurality of dielectric walls **19** are each formed between a corresponding pair of the first and second stacks **14**, **15**. FIG. **8** is a schematic view similar to FIG. **2** but further illustrating the dielectric walls **19**. FIGS. **8** to **10** are views respectively similar to FIGS. **2** to **4**, but illustrating the structures after step **102**.

(22) In some other not shown embodiments, a lower end of each of the dielectric walls **19** shown in FIG. **9** may further extend downwardly to be in contact with the substrate **10** such that each of the dielectric walls **19** may be formed between a corresponding pair of the first and second fins **11**, **12**. In some embodiments, each of the dielectric walls **19** may be formed as a single layer structure or a multi-layered structure. In some embodiments, the dielectric walls **19** may include a suitable low-k material and/or a high-k material (such as the examples described in the preceding paragraph). Other suitable materials for the dielectric walls **19** are within the contemplated scope of the present disclosure.

(23) In some embodiments, step **102** may include sub-steps **1021** and **1022**.

(24) In sub-step **1021**, as shown in FIGS. **6** and **7**, a dielectric material layer **191** for forming the dielectric walls **19** is formed over the structure obtained after step **101** by, for example, physical vapor deposition (PVD), chemical vapor deposition (CVD), atomic layer deposition (ALD), molecular-beam deposition (MBD), or other suitable processes so as to fill a gap **190** between each pair of the first and second stacks **14**, **15** (see FIGS. **2** and **3**).

(25) In sub-step **1022**, the dielectric material layer **191** is etched back using a wet etching process, other suitable process, or combinations thereof, to remain portions of the dielectric layer **191** between each pair of the stacks **14**, **15** (see FIG. **6**) so as to obtain the dielectric walls **19**. In some embodiments, as shown in FIGS. **8** and **9**, a first dielectric wall **19A** is formed between a pair of the first and second stacks **14**, **15** which is disposed on the first and second fins **11**, **12** of the first pair **1A**, and a second dielectric wall **19B** is formed between the other pair of the first and second stacks **14**, **15** which is disposed on the first and second fins **11**, **12** of the second pair **1B**.

(26) In some embodiments, the gap **190** (see FIG. **3**) between each pair of the stacks **14**, **15** has a gap width (**W0**) ranging from about 10 nm to about 40 nm, and the gap width (**W0**) may determine a wall width (**WW1**) of each of the dielectric walls **19** which is formed between a corresponding pair of the stacks **14**, **15**. In some embodiments, the wall width (**WW1**) may range from about 10

nm to about 40 nm.

(27) In some embodiments, as shown in FIGS. 3 and 4, two adjacent pairs of the stacks **14**, **15** are spaced apart in the Y direction by a distance (DO) not less than about 40 nm, and two adjacent ones of the third stacks **16** are spaced apart in the Y direction by a distance (D1) not less than about 40 nm, such that during etching back of the dielectric material layer **191**, portions of the dielectric material layer **191** between the two adjacent pairs of the stacks **14**, **15** and between the two adjacent ones of the third stacks **16** may be removed.

(28) In some embodiments, during etching back of the dielectric material layer **191**, the mask layers **183** of the first, second and third stacks **14**, **15**, **16** shown in FIGS. 6 and 7 are also removed. In this case, an etchant which has an etching selectivity to the material of the mask layers **183** higher than an etching selectivity to the materials of other elements may be used, and the dielectric material of the mask layers **183** may be different from the dielectric materials of the dielectric material layer **191** and the isolation regions **17**. Other suitable processes for forming the dielectric walls **19** are within the contemplated scope of the present disclosure. After step **102**, the remaining portions of the first, second and third stacks **14**, **15**, **16** are denoted by **14A**, **15A** and **16A**, respectively.

(29) FIG. 11 is similar to FIG. 5 but illustrating the structure after step **102** in accordance with some other embodiments. It can be seen that a single dielectric wall **19** is formed among the fins **11**, **12**, **13**.

(30) Since the semiconductor structure made by the method **100** may have a plurality of layout designs based on application requirements, in the following steps, the structures shown in FIGS. 8 to **10** are to be further illustrated, and the structures shown in FIG. 11 will not be further illustrated for the sake of brevity.

(31) Referring to FIG. 1 and the examples illustrated in FIGS. 12, 13, and 14, the method **100** proceeds to step **103**, where a plurality of dummy gate portions **20** are formed over the structure obtained after step **102**. FIG. 12 is a schematic view similar to FIG. 8 but further illustrating the dummy gate portions **20**. FIGS. 12 to 14 are views respectively similar to FIGS. 8 to 10, but illustrating the structures after step **103**. FIGS. 13 and 14 are cross-sectional views respectively taken along lines C-C' and D-D' of FIG. 12 in accordance with some embodiments but further illustrating the other elements omitted in FIG. 12. The dummy gate portions **20** are each elongated in the Y direction, and are spaced apart from each other in the X direction.

(32) For the purposes of simplicity and clarity, in FIG. 12, the number of the dummy gate portions **20** is five. For better illustration, as shown in FIGS. 12 to 14, (i) the dummy gate portions, which are disposed over the first and second fins **11**, **12**, the first and second stacks **14**, **15** and the dielectric walls **19**, are denoted by **20A**, **20B**, (ii) the dummy gate portion, which is disposed to over the first, second and third fins **11**, **12**, **13** and the first, second and third stacks **14**, **15**, **16**, is denoted by **20C**, and (iii) the dummy gate portions, which are disposed over the third fins **13** and the third stacks **16A**, are denoted by **20D**, **20E**. In practical, the number of the dummy gate portions **20** are determined according to application requirements.

(33) Each of the dummy gate portions **20** has a poly width in the X direction. The poly width of each of the dummy gate portions **20** will affect a gate width (GW1, GW2) in the X direction of a corresponding one of gate structures **30** (see FIG. 20) to be subsequently formed, and is positively correlated with a channel length (CL11, CL12, CL2) in the X direction of the channel features **182A** (see FIG. 16).

(34) In some embodiments, each of the dummy gate portions **20D**, **20E** may have a second poly width (PW2) that is greater than a first poly width (PW1) of each of the dummy gate portions **20A**, **20B**, **20C**. In some embodiments, a ratio of the second poly width (PW2) to the first poly width (PW1) may range from about 1.1 to about 1.5.

(35) Each of the dummy gate portions **20A**, **20B** has a side surface which is distal from the dummy gate portion **20C**, and the side surfaces of two adjacent ones of the dummy gate portions **20A**, **20B**

are spaced apart by a first pitch (CPP1). Each of the dummy gate portions **20D**, **20E** has a side surface which is distal from the dummy gate portion **20C**, and the side surfaces of two adjacent ones of the dummy gate portions **20D**, **20E** are spaced apart by a second pitch (CPP2). The first and second pitches (CPP1, CPP2), which are adjustable and determined in step **103**, will affect periodicity of distribution of the gate structures **30** (see FIG. **20**) to be subsequently formed. In some embodiments, the first pitch (CPP1) may be the same as the second pitch (CPP2). In some other embodiments, as shown in FIG. **12**, the second pitch (CPP2) is greater than the first pitch (CPP1). In some embodiments, the second pitch (CPP2) may be greater than the first pitch (CPP1) by about 5% to about 20%. That is, a ratio of the second pitch (CPP2) to the first pitch (CPP1) may range from about 1.05 to about 1.2.

(36) In some embodiments, each of the dummy gate portions **20** may include, in a direction away from the substrate **10**, a dummy gate dielectric **201**, a dummy gate electrode **202**, a polish stop layer **203**, and a hard mask **204**. In some embodiments, each of the hard mask **434** and the polish stop layer **433** may independently include silicon nitride, silicon oxide, silicon oxynitride, or combinations thereof; the dummy gate electrode **432** may include polycrystalline silicon, single crystalline silicon, amorphous silicon, or combinations thereof; and the dummy gate dielectric **431** may include silicon oxide, silicon nitride, silicon oxynitride, a suitable high-k material (such as the examples described in the preceding paragraph), or combinations thereof. In some embodiments, step **103** for forming the dummy gate portions **20** may include (i) sequentially depositing two layers of materials for forming the dummy gate dielectric **201** and the dummy gate electrode **202** over the structure obtained after step **102** using PVD, CVD, ALD or other suitable processes, (ii) performing a planarization process using, for example, CMP to form a planar surface, (iii) sequentially depositing another two layers of materials for forming the polish stop layer **203** and the hard mask **204** using PVD, CVD, ALD or other suitable processes, and (iv) patterning the four layers of materials through a patterned photoresist layer using a suitable etching process (such as a dry etching process, a wet etching process, other suitable processes, or combinations thereof). Other suitable materials and/or processes for forming the dummy gate portions **20** are within the contemplated scope of the present disclosure.

(37) Referring to FIG. **1** and the examples illustrated in FIGS. **13** to **16**, the method **100** proceeds to step **104**, where a plurality of gate spacers **21**, a plurality of fin sidewalls **22**, a plurality of source/drain recesses **23** and a plurality of inner spacers **24** are formed. FIG. **15** is similar to FIG. **12** but further illustrating the gate spacers **21** and the fin sidewalls **22** in accordance with some embodiments. FIG. **16** is a cross-sectional view taken along line E-E' of FIG. **15** in accordance with some embodiments but further illustrating the other elements omitted in FIG. **15**. For the purposes of simplicity and clarity, the dummy gate portions **20A**, **20E** and corresponding elements adjacent thereto are shown in FIG. **16**, and other elements not adjacent thereto are omitted. The structures shown in FIGS. **13** and **14** are substantially not changed after step **104**.

(38) In some embodiments, step **104** includes sub-steps **1041** to **1044**.

(39) In sub-step **1041**, each pair of the gate spacers **21** are respectively formed at the two opposite sides of a corresponding one of the dummy gate portions **20** in the X direction. In some embodiments, each of the gate spacers **21** may be formed as a single layer structure or a multi-layered structure. In some embodiments, the gate spacers **21** may be formed by conformally depositing dielectric material(s) for forming the gate spacers **21** over the structure obtained after step **103** using, for example, CVD, ALD, or other suitable deposition techniques, followed by an anisotropic dry etching process until an upper surface of each of the dummy gate portions **20** is exposed such that the remaining dielectric material(s) serve as the gate spacers **21**.

(40) In some embodiments, referring to FIGS. **13** to **15**, a first fin unit, a second fin unit, and three fin assemblies are obtained after sub-step **1041**. The first fin unit includes the first and second fins **11**, **12** of the first pair **1A**, a corresponding pair of the stacks **14A**, **15A** disposed on the first and second fins **11**, **12** of the first pair **1A**, and the first dielectric wall **19A**, and has a plurality of

exposed portions exposed from the dummy gate portions **20** and the gate spacers **21**. The second fin unit includes the first and second fins **11**, **12** of the second pair **1B**, a corresponding pair of the stacks **14A**, **15A** disposed on the first and second fins **11**, **12** of the second pair **1B**, and the second dielectric wall **19B**, and has a plurality of exposed portions exposed from the dummy gate portions **20** and the gate spacers **21**. Each of the three fin assemblies includes one of the third fins **13** and a corresponding one of the third stacks **16A** disposed thereon, and has a plurality of exposed portions exposed from the dummy gate portions **20** and the gate spacers **21**. In some embodiments, during formation of the gate spacers **21**, a plurality pairs of the fin sidewalls **22** are formed. Each pair of the fin sidewalls **22** is formed at two opposite sides of a corresponding one of the first fin unit, the second fin unit and the three fin assemblies in the Y direction. Each of the fin sidewalls **22** has a plurality of sidewall segments which are disposed aside corresponding ones of the exposed portions. In some embodiments, the dielectric materials for forming the gate spacers **21** and the fin sidewalls **22** may include a suitable low-k material (such as the examples described in the preceding paragraph), but is not limited thereto. Other suitable materials for the gate spacers **21** and the fin sidewalls **22** are within the contemplated scope of the present disclosure.

(41) In sub-step **1042**, the exposed portions of the first and second fin units and the three fin assemblies are respectively etched away to form a plurality of source/drain recesses **23** using dry etching, wet etching, other suitable processes, or combinations thereof. After sub-step **1042**, the sacrificial layers **181** and the channel layers **182** (see FIGS. **3** and **4**) are respectively patterned into sacrificial features (not shown) and the channel features **182A** (see FIG. **16**).

(42) As shown in FIG. **16**, after sub-step **1042**, the channel layers **182** of the first remaining stacks **14A** shown in FIG. **9** are patterned into first channel features **1821**, each of which has a channel length (CL**11**) in the X direction, and the channel layers **182** of the second remaining stacks **15A** shown in FIG. **9** are patterned into second channel features **1822**, each of which has a channel length (CL**12**) in the X direction. The channel layers **182** of the third remaining stack **16A** disposed on the main fin **130** are patterned into third channel features **1823** (see FIG. **14**), the channel layers **182** of the third remaining stack **16A** disposed on the first auxiliary fin **131** are patterned into fourth channel features **1824** (see FIGS. **14** and **16**), and the channel layers **182** of the third remaining stack **16A** disposed on the second auxiliary fin **131** are patterned into fifth channel features **1825** (see FIG. **14**). Each of the channel features **1823**, **1824**, **1825** has a channel length (CL**2**) in the X direction. In some embodiments, the channel length (CL**2**) of each of the channel features **1823**, **1824**, **1825** is greater than the channel length (CL**11**, CL**12**) of each of the first and second channel features **1821**, **1822**.

(43) As shown in FIGS. **13** and **14**, each of the channel features **1821**, **1822**, **1823**, **1824**, **1825** has a channel width (CW**11**, CW**12**, CW**20**, CW**21**, CW**22**) in the Y direction. In some embodiments, as shown in FIG. **13**, each of the first channel features **1821** may have a channel width (CW**11**) the same as a channel width (CW**12**) of each of the second channel features **1822**. In some other embodiments, each of the first channel features **1821** may have a channel width (CW**11**) different from a channel width (CW**12**) of each of the second channel features **1822**. In some embodiments, a ratio of the wall width (WW**1**) of one of the dielectric walls **19** to a channel width (CW**11**, CW**12**) of each of the channel features **1821**, **1822** disposed adjacent to the one of the dielectric walls **19** may independently range from about 0.2 to about 3.

(44) In some embodiments, at least one stack of the channel features **1823**, **1824**, **1825** has a channel width (CW**20**, CW**21**, CW**22**) that is greater than a channel width (CW**11**, CW**12**) of each of the channel features **1821**, **1822**.

(45) In some embodiments, when each of the first channel features **1821** has a channel width (CW**11**) different from a channel width (CW**12**) of each of the second channel features **1822**, a ratio of the channel width (CW**11**, CW**12**) of each of the channel features **1821**, **1822** to the channel width (CW**20**, CW**21**, CW**22**) of the at least one stack of the channel features **1823**, **1824**, **1825** may independently range from about 0.2 to about 0.9.

(46) In some embodiments, when each of the first channel features **1821** has a channel width (CW11) the same as channel width (CW12) of each of the second channel features **1822**, a ratio of the channel width (CW11, CW12) of each of the channel features **1821**, **1822** to the channel width (CW20, CW21, CW22) of the at least one stack of the channel features **1823**, **1824**, **1825** may independently range from about 0.2 to about 0.5.

(47) In some embodiments, a sum of the channel width (CW11), the channel width (CW12) and the wall width (WW1) may be smaller than, equal to, or greater than the channel width (CW20).

(48) In some embodiments, each of the first channel features **1821** has a channel width (CW11) ranging from about 5 nm to about 60 nm. In some embodiments, each of the second channel features **1822** has a channel width (CW12) ranging from about 5 nm to about 60 nm. In some embodiments, at least one stack of the channel features **1823**, **1824**, **1825** has a channel width (CW20, CW21, CW22) ranging from about 6 nm to about 120 nm.

(49) In some embodiments, each of the channel features **182A** disposed on one of the third fins **13** may have a channel width the same as or different from that of each of the channel features **182A** disposed on another one of the third fins **13**. For example, as shown in FIG. **14**, the third channel features **1823** have a channel width (CW20) that is greater than a channel width (CW21, CW22) of each of the fourth and fifth channel features **1824**, **1825**.

(50) In some embodiments, in the case that the first channel features **1821** disposed on the first fin **11** of the first pair **1A** is designed for forming an n-FET, and that the second channel features **1822** disposed on the second fin **12** of the first pair **1A** is designed for forming a p-FET, the first channel features **1821** may each have an N1-channel width in the Y direction, and the second channel features **1822** may each have a P2-channel width in the Y direction. A ratio of the N1-channel width to the P2-channel width may range from about 0.4 to about 2.5. In some embodiments, in the case that the third channel features **1823** is designed for forming an n-FET, and that the fourth channel features **1824** is designed for forming a p-FET, the third channel features **1823** may each have an N3-channel width in the Y direction, and the fourth channel features **1824** may each have a P4-channel width in the Y direction. A ratio of the N3-channel width to the P4-channel width may range from about 0.4 to about 2.5.

(51) In some embodiments, as shown in FIG. **16**, each of the source/drain recesses **23** extends into an upper part of a corresponding one of the fins **11**, **12**, **13**. In some embodiments, the fin sidewalls **22** are recessed during formation of the source/drain recesses **23**, and thus have a reduced height compared to the height of the fin sidewalls **22** obtained in sub-step **1041**.

(52) In sub-step **1043**, the sacrificial features are recessed through the source/drain recesses **23** to form lateral recesses (not shown) by an isotropic etching process, such as wet etching, or other suitable etching techniques. After sub-step **1043**, the remaining sacrificial features are denoted by **181A** (see FIG. **16**).

(53) In sub-step **1044**, referring to FIG. **16**, the inner spacers **24** are formed to respectively cover two opposite ends of the remaining sacrificial features **181A** in the X direction. In some embodiments, the inner spacers **24** may be formed by (i) depositing a dielectric material (not shown) for forming the inner spacers **24** on the structure obtained after sub-step **1043** to fill the lateral recesses by CVD, ALD, or other suitable deposition techniques, and (ii) removing excess portions of the dielectric material for forming the inner spacers **24** by an etching process, for example, but not limited to, a wet etching process, a dry etching process, other suitable etching techniques, or combinations thereof, such that the inner spacers **24** are respectively formed in the lateral recesses. In some embodiments, the dielectric material for forming the inner spacers **24** includes silicon oxide, silicon nitride, silicon oxynitride, other suitable dielectric materials, or combinations thereof. Other dielectric materials suitable for the inner spacers **24** are within the contemplated scope of the present disclosure.

(54) Referring to FIG. **1** and the examples illustrated in FIGS. **13**, **14**, **17** and **18**, the method **100** proceeds to step **105**, where a plurality of source/drain features **25** are respectively formed in the

source/drain recesses **23** shown in FIG. **16** by an epitaxial growth process including CVD, molecular-beam epitaxy (MBE), an epitaxial deposition/partial etch process, such as a cyclic deposition-etch (CDE) process and/or a selective epitaxial growth (SEG) process, but is not limited thereto. Each pair of source/drain features **25** are formed at two opposite sides of the channel features **182A** in the X direction, such that each of the channel features **182A** interconnects a corresponding pair of the source/drain features **25**. It is noted that each of the source/drain features **25** may refer to a source or a drain, individually or collectively dependent upon the context. FIG. **17** is a schematic view similar to FIG. **15** but further illustrating the source/drain features **25**, and the gate spacers **21** and the fin sidewalls **22** shown in FIG. **15** are omitted for the sake of simplicity and clarity. FIGS. **17** and **18** are views similar to those of FIGS. **15** and **16**, but illustrating the structure after step **105**. The structures shown in FIGS. **13** and **14** are substantially not changed after step **105**.

(55) Each pair of the source/drain features **25** may be independently doped with an n-type impurity or a p-type impurity, and may be formed as a single layer structure or a multi-layered structure having several sub-layers with different doping concentration.

(56) In some embodiments, as shown in FIG. **17**, first source/drain features **251** and second source/drain features **252** are respectively formed on the first fin **11** and the second fin **12** of each pair **1A**, **1B**. Third source/drain features **253**, fourth source/drain features **254** and fifth source/drain features **255** are respectively formed on the main fin **130**, the first auxiliary fin **131** and the second auxiliary fin **132**.

(57) The source/drain features **25** formed on different fins **11**, **12**, **13** may have different conductivity types. For example, the first source/drain features **251** which are disposed on the first fin **11** of the first pair **1A**, the second source/drain features **252** which are disposed on the second fin **12** of the second pair **1B**, the fourth source/drain features **254**, and the fifth source/drain features **255** may each have an n-type conductivity so as to function as a source/drain of an n-FET, and may include single crystalline silicon, polycrystalline silicon or other suitable materials doped with an n-type impurity. The n-type impurity may be, for example, but not limited to, nitrogen (N), phosphorous (P), arsenic (As), antimony (Sb), other suitable materials, or combinations thereof. In addition, the second source/drain features **252** which are disposed on the second fin **12** of the first pair **1A**, the first source/drain features **251** which are disposed on the second fin **12** of the second pair **1B**, and the third source/drain features **253** may each have a p-type conductivity so as to function as a source/drain of a p-FET, and may include single crystalline or polycrystalline silicon, single crystalline or polycrystalline silicon germanium, or other suitable materials doped with a p-type impurity. The p-type impurity may be, for example, but not limited to, boron (B), aluminum (Al), gallium (Ga), indium (In), other suitable materials, or combinations thereof.

(58) Referring to FIG. **1** and the examples illustrated in FIGS. **13**, **14** and **19**, the method **100** proceeds to step **106**, where a plurality of contact etching stop features **26** and a plurality of inter-layer dielectric (ILD) features **27** are sequentially and respectively formed on the source/drain features **25**. FIG. **19** is a view similar to that of FIG. **18**, but illustrating the structure after step **106**. The structures shown in FIGS. **13** and **14** are substantially not changed after step **106**.

(59) In some embodiments, step **106** is performed by sequentially depositing a contact etching stop layer (not shown) and an ILD layer (not shown) sequentially over the structure shown in FIG. **18** using a blanket deposition process, such as, but not limited to, CVD or molecular layer deposition (MLD), followed by a planarization process, for example, but not limited to, CMP, thereby removing the hard mask **204** and the polish stop layer **203** (see FIG. **18**) of each of the dummy gate portions **20** and exposing the dummy gate electrode **202** of each of the dummy gate portions **20**. Thereafter, the contact etching stop layer is formed into the contact etching stop features **26** and the ILD layer is formed into the ILD features **27**. In some embodiments, the contact etching stop layer for forming the contact etching stop features **26** may include, for example, but not limited to, silicon nitride, carbon-doped silicon nitride, other suitable materials, or combinations thereof. In

some embodiments, the ILD layer for forming the ILD features **27** may include a dielectric material such as, but not limited to, silicon oxide, silicon nitride, silicon oxynitride, other suitable materials, or combinations thereof. Other suitable materials for the contact etching stop features **26** and the ILD features **27** are within the contemplated scope of the present disclosure.

(60) Referring to FIG. **1** and the examples illustrated in FIGS. **20** to **23**, the method **100** proceeds to step **107**, where a replacement gate process is performed such that the remaining dummy gate portions **20** (see FIG. **19**) are respectively replaced with a plurality of gate structures **30** each including a gate dielectric layer **31** and a gate feature **32** disposed on the gate dielectric layer **31**. FIG. **20** is a schematic view similar to FIG. **17** but the remaining dummy gate portions **20** are replaced with the gate structures **30**, respectively. FIGS. **20** to **23** are views similar to those of FIGS. **17**, **19**, **13** and **14**, but illustrating the structure after step **107**.

(61) In some embodiments, step **107** includes (i) removing the dummy gate electrode **202** and the dummy gate dielectric **201** of each of the remaining dummy gate portions **20** to form a plurality of cavities (not shown) using dry etching, wet etching, other suitable processes, or combinations thereof, (ii) sequentially depositing materials for forming the gate dielectric layer **31** and the gate feature **32** to fill the cavities by a blanket deposition process, such as ALD, CVD or MLD, and (iii) performing a planarization process, for example, but not limited to, CMP, to remove excesses of the materials for forming the gate feature **32** and the gate dielectric layer **31** and to expose the ILD features **27**, and (iv) etching back the materials for forming the gate dielectric layer **31** and the gate feature **32** using for example, but not limited to, dry etching, wet etching, other suitable processes, or combinations thereof, thereby obtaining the gate structures **30** respectively in the cavities.

(62) In some embodiments, the gate dielectric layer **31** of each of the gate structures **30** includes silicon oxide, silicon nitride, silicon oxynitride, a suitable high-k material (such as the examples described in the preceding paragraph), other suitable materials, or combinations thereof. Other suitable materials for the gate dielectric layer **31** are within the contemplated scope of the present disclosure. In some embodiments, the gate feature **32** of each of the gate structures **30** may be configured as a multi-layered structure including at least one work function metal which is provided for adjusting threshold voltage of an n-FET or a p-FET, an electrically conductive material having a low resistance which is provided for reducing electrical conductivity of the gate feature **32**, other suitable materials, or combinations thereof. In some embodiments, the work function metal of the gate feature **32** of each of the gate structures **30** for forming an n-FET may be different from that for forming a p-FET so as to permit the n-FET and the p-FET to have different threshold voltages. Other suitable methods for adjusting the threshold voltages are within the contemplated scope of the present disclosure. In some embodiments, the gate feature **32** includes a metal material (e.g., tungsten (W), titanium (Ti), tantalum (Ta), aluminum (Al), or ruthenium (Ru)), metal-containing nitrides (e.g., titanium nitride (TiN), or tantalum nitride (TaN)), metal-containing silicides (e.g., nickel silicide (NiSi)), metal-containing carbides (e.g., tantalum carbide (TaC)), or combinations thereof. Other suitable materials for the gate feature **32** are within the contemplated scope of the present disclosure.

(63) In some embodiments, step **107** further includes depositing a dielectric material for forming a plurality of self-aligned dielectric features **33** on the structure obtained after formation of the gate structures **30** using a blanket deposition process, such as, but not limited to, CVD, ALD, or other suitable deposition techniques, followed by a planarization process, for example, but not limited to, CMP, or other suitable processes, to expose the ILD features **27**, thereby obtaining the self-aligned dielectric features **33** respectively disposed on the gate structures **30**. In some embodiments, the dielectric material for forming the self-aligned dielectric features **33** include silicon oxide, silicon nitride, silicon oxynitride, but is not limited thereto.

(64) After step **107**, as shown in FIG. **20**, the remaining dummy gate portions **20A** to **20E** (see FIG. **17**) are replaced with the gate structures **30A** to **30E**, respectively. Each of the gate structures **30A** to **30E** has a gate width in the X direction. In some embodiments, each of the gate structures **30D**,

30E may have a second gate width (GW2) that is greater than a first gate width (GW1) of each of the gate structures **30A**, **30B**, **30C**. In some embodiments, a ratio of the second gate width (GW2) to the first gate width (GW1) may range from about 1.1 to about 1.5.

(65) Each of the gate structures **30A**, **30B** has a side surface which is distal from the gate structure **30C**, and the side surfaces of two adjacent ones of the gate structures **30A**, **30B** are spaced apart by a third pitch (CPP3). Each of the gate structures **30D**, **30E** has a side surface which is distal from the gate structure **30C**, and the side surfaces of two adjacent ones of the gate structure **30D**, **30E** are spaced apart by a fourth pitch (CPP4). The third and fourth pitches (CPP3, CPP4) are substantially the same as the first and second pitches (CPP1, CPP2), respectively, as described above with reference to FIG. 12. In some embodiments, the third pitch (CPP3) may be the same as the fourth pitch (CPP4). In some other embodiments, as shown in FIG. 20, the fourth pitch (CPP4) is greater than the third pitch (CPP3). In some embodiments, the fourth pitch (CPP4) may be greater than the third pitch (CPP3) by about 5% to about 20%. That is, a ratio of the fourth pitch (CPP4) to the third pitch (CPP3) may range from about 1.05 to about 1.2.

(66) For each of the gate structures **30A**, **30B** which is disposed over the first and second fins **11**, **12** (the gate structure **30A** is shown in FIG. 22), the gate dielectric layer **31** is disposed to separate the gate feature **32** from the first and second channel features **1821**, **1822**, corresponding ones of the inner spacers **24** (see FIG. 21) and the dielectric walls **19**. Each of the gate structures **30A**, **30B** includes a first real gate portion **301**, a second real gate portion **302**, a third real gate portion **303** and a fourth real gate portion **304** displaced from one another in the Y direction. The first real gate portion **301** is disposed around the first channel features **1821** which are disposed over the first fin **11** of the first pair **1A**. The second real gate portion **302** is disposed around the second channel features **1822** which are disposed over the second fin **12** of the first pair **1A**. The third real gate portion **303** is disposed around the first channel features **1821** which are disposed over the first fin **11** of the second pair **1B**. The fourth real gate portion **304** is disposed around the second channel features **1822** which are disposed over the second fin **12** of the second pair **1B**.

(67) For each of the gate structures **30D**, **30E** which is disposed over the third fins **13** (the gate structure **30E** is shown in FIG. 23), the gate dielectric layer **31** is disposed to separate the gate feature **32** from the channel features **1823**, **1824**, **1825** and corresponding ones of the inner spacers **24**. Each of the gate structures **30D**, **30E** includes a fifth real gate portion **305**, a sixth real gate portion **306** and a seventh real gate portion **307** displaced from one another in the Y direction. The fifth real gate portion **305** is disposed to surround the third channel features **1823**. The sixth real gate portion **306** is disposed to surround the fourth channel features **1824**. The seventh real gate portion **307** is disposed to surround the fifth channel features **1825**.

(68) As shown in FIG. 20, the gate structure **30C** includes a first portion and a second portion displaced from the first portion in the X direction. The first portion is located in position above the first and second fins **11**, **12**, and the second portion is located in position above the third fins **13**. Hence, the first portion of the gate structure **30C** is disposed around corresponding ones of the channel features **182A** which are disposed over the first and second fins **11**, **12**, and the second portion of the gate structure **30C** is disposed to surround corresponding ones of the channel features **182A** which are disposed over the third fins **13**.

(69) In some embodiments, at least one device unit and at least one device assembly is thus formed on the substrate **10** after step **107**. The at least one device unit includes (i) a single first fin **11** and a single second fin **12** spaced apart from each other in the Y direction, (ii) at least one first device **41** and at least one second device **42** respectively formed the first and second fins **11**, **12**, and (iii) a single dielectric wall **19** disposed between the first and second devices **41**, **42**. The at least one device assembly includes (i) a single third fin **13** which is in direct contact with at least one of the first and second fins **11**, **12**, and (ii) at least one third device **43** formed on the third fin **13**.

(70) The number of the device unit and the number of the device assembly may vary according to practical requirements. For example, as shown in FIG. 20, two devices units **401**, **402**, and three

device assemblies **403**, **404**, **405** are formed on the substrate **10**.

(71) As shown in FIGS. **20** and **22**, the device unit **401** includes (i) the first and second fins **11**, **12** of the first pair **1A** which are spaced apart from each other in the Y direction, (ii) the first dielectric wall **19A** which has a first wall surface (**51**) and a second wall surface (**S2**), and (iii) at least one first device **41** and at least one second device **42** which are respectively formed on the first and second fins **11**, **12** of the first pair **1A**. In some embodiments, the first wall surface (**51**) and the second wall surface (**S2**) are opposite to each other.

(72) The at least one first device **41** in the device unit **401** includes (i) the first channel features **1821** extending away from the first wall surface (**51**) of the first dielectric wall **19A** to be disposed over the first fin **11** of the first pair **1A** so as to permit the first channel features **1821** to be spaced apart from each other in the Z direction (see FIG. **22**), (ii) a pair of the first source/drain features **251** which are disposed on the first fin **11** of the first pair **1A**, and which are spaced apart from each other in the X direction such that each of the first channel features **1821** interconnects the pair of the first source/drain features **251** (see FIG. **21**), and (iii) the first real gate portion **301** of a corresponding one of the gate structures **30A**, **30B** such that the pair of the first source/drain features **251** are respectively located at two opposite sides of the first real gate portion **301** of the corresponding gate structure **30A**, **30B** in the X direction.

(73) The at least one second device **42** in the device unit **401** includes (i) the second channel features **1822** extending away from the second wall surface **S2** of the first dielectric wall **19A** to be disposed over the second fin **12** of the first pair **1A** so as to permit the second channel features **1822** to be spaced apart from each other in the Z direction (see FIG. **22**), (ii) a pair of the second source/drain features **252** which are disposed on the second fin **12** of the first pair **1A**, and which are spaced apart from each other in the X direction such that each of the second channel features **1822** interconnects the pair of the second source/drain features **252** (see FIG. **21**), and (iii) the second real gate portion **302** of a corresponding one of the gate structures **30A**, **30B** such that the pair of the second source/drain features **252** are respectively located at two opposite sides of the second real gate portion **302** of the corresponding gate structure **30A**, **30B** in the X direction. In some embodiments, in the device unit **401**, the second real gate portion **302** of the at least one second device **42** and the first real gate portion **301** of the at least one first device **41** may extend toward each other in the Y direction to merge on the first dielectric wall **19A** (see FIGS. **20** and **22**).

(74) As shown in FIGS. **20** and **22**, the device unit **402** includes (i) the first and second fins **11**, **12** of the second pair **1B** which are spaced apart from each other in the Y direction, (ii) the second dielectric wall **19B** which has a first wall surface (**51**) and a second wall surface (**S2**), and (iii) at least one first device **41** and at least one second device **42** which are respectively formed on the first and second fins **11**, **12** of the second pair **1B**.

(75) The at least one first device **41** in the device unit **402** includes (i) the first channel features **1821** extending away from the first wall surface (**51**) of the second dielectric wall **19B** to be disposed over the first fin **11** of the second pair **1B** so as to permit the first channel features **1821** to be spaced apart from each other in the Z direction, (ii) a pair of the first source/drain features **251** which are disposed on the first fin **11** of the second pair **1B**, and which are spaced apart from each other in the X direction such that each of the first channel features **1821** interconnects the pair of the first source/drain features **251**, and (iii) the third real gate portion **303** of a corresponding one of the gate structures **30A**, **30B** such that the pair of the first source/drain features **251** are respectively located at two opposite sides of the third real gate portion **303** of the corresponding gate structure **30A**, **30B** in the X direction.

(76) The at least one second device **42** in the device unit **402** includes the second channel features **1822** extending away from the second wall surface (**S2**) of the second dielectric wall **19B** to be disposed over the second fin **12** of the second pair **1B** so as to permit the second channel features **1822** to be spaced apart from each other in the Z direction, (ii) a pair of the second source/drain features **252** which are disposed on the second fin **12** of the second pair **1B**, and which are spaced

apart from each other in the X direction such that each of the second channel features **1822** interconnects the pair of the second source/drain features **252**, and (iii) the fourth real gate portion **304** of a corresponding one of the gate structures **30A**, **30B** such that the pair of the second source/drain features **252** are respectively located at two opposite sides of the fourth real gate portion **304** of the corresponding gate structure **30A**, **30B** in the X direction. In some embodiments, in the device unit **402**, the fourth real gate portion **304** of the at least one second device **42** and the third real gate portion **303** of the at least one first device **41** may extend toward each other in the Y direction to merge on the second dielectric wall **19B**. In some embodiments, the second real gate portion **302** of the at least one second device **42** in the device unit **401** and the third real gate portion **303** of the at least one first device **41** in the device unit **402** may extend toward each other in the Y direction to merge on one of the isolation regions **17** which is disposed between the second fin **12** of the first pair **1A** of and the first fin **11** of the second pair **1B**.

(77) The device unit **403** includes the main fin **130** which is in direct contact with the second fin **12** of the first pair **1A** and the first fin **11** of the second pair **1B**, and at least one third device **43** which is formed on the main fin **130**.

(78) As shown in FIGS. **20** and **23**, the at least one third device **43** in the device unit **403** includes the third channel features **1823** which are spaced apart from each other in the Z direction, a pair of the third source/drain features **253** which are spaced apart from each other in the X direction such that each of the third channel features **1823** interconnects the pair of the third source/drain features **253**, and the fifth real gate portion **305** of a corresponding one of the gate structures **30D**, **30E** such that the pair of the third source/drain features **253** are respectively located at two opposite sides of the fifth real gate portion **305** of the corresponding gate structure **30D**, **30E** in the X direction.

(79) The device unit **404** includes the first auxiliary fin **131** which is in direct contact with the first fin **11** of the first pair **1A**, and at least one third device **43** which is formed on the first auxiliary fin **131**.

(80) As shown in FIGS. **20** and **23**, the at least one third device **43** in the device unit **404** includes the fourth channel features **1824** which are spaced apart from each other in the Z direction, a pair of the fourth source/drain features **254** which are spaced apart from each other in the X direction such that each of the fourth channel features **1824** interconnects the pair of the fourth source/drain features **254**, and the sixth real gate portion **306** of a corresponding one of the gate structures **30D**, **30E** such that the pair of the fourth source/drain features **254** are respectively located at two opposite sides of the sixth real gate portion **306** of the corresponding gate structure **30D**, **30E** in the X direction.

(81) The device unit **405** includes the second auxiliary fin **132** which is in direct contact with the second fin **12** of the second pair **1B**, and at least one third device **43** which is formed on the second auxiliary fin **132**.

(82) As shown in FIGS. **20** and **23**, the at least one third device **43** in the device unit **405** includes the fifth channel features **1825** which are disposed over the second auxiliary fin **132**, and which are spaced apart from each other in the Z direction, a pair of the fifth source/drain features **255** which are spaced apart from each other in the X direction such that each of the fifth channel features **1825** interconnects the pair of the fifth source/drain features **255**, and the seventh real gate portion **307** of a corresponding one of the gate structures **30D**, **30E** such that the pair of the source/drain features **255** are respectively located at two opposite sides of the seventh real gate portion **307** of the corresponding gate structure **30D**, **30E** in the X direction.

(83) In some embodiments, the fifth real gate portion **305** of the at least one third device **43** in the device unit **403** and the sixth real gate portion **306** of the at least one third device **43** in the device unit **404** extend toward each other in the Y direction to merge on one of the isolation regions **17** which is disposed between the main fin **130** and the first auxiliary fin **131**. In some embodiments, the fifth real gate portion **305** of the at least one third device **43** in the device unit **403** and the seventh real gate portion **307** of the at least one third device **43** in the device unit **405** extend

toward each other in the Y direction to merge on one of the isolation regions **17** which is disposed between the main fin **130** and the second auxiliary fin **132**.

(84) In some embodiments, the at least one first device **41** in the device unit **401**, the at least one second device **42** in the device unit **402**, and the third devices **43** in the device assemblies **404**, **405** serve as n-FETs, while the at least one second device **42** in the device unit **401**, the at least one first device **41** in the device unit **402**, and the at least one third device **43** in the device assembly **403** serve as p-FETs.

(85) Referring to FIG. **1** and the examples illustrated in FIGS. **24** to **26**, the method **100** proceeds to step **108**, where an isolation feature **50** is formed over the substrate **10** to permit the third devices **43** to be electrically isolated from the first and second devices **41**, **42**. FIG. **24** is a schematic view similar to FIG. **20** but illustrating the structure after step **108**. FIGS. **25** and **26** are a cross-sectional views respectively taken along lines F-F' and G-G' of FIG. **24** in accordance with some embodiments but further illustrating the other elements omitted in FIG. **24**.

(86) In some embodiments, as shown in FIG. **24**, the isolation feature **50** includes a single gate isolation portion **51** which is made of a dielectric material, which is elongated in the Y direction through the first and second fins **11**, **12** of the device units **401**, **402** and through the third fins **13** of the device assemblies **403**, **404**, **405**, and which is spaced apart from each two adjacent ones of the gate structures **30B**, **30D** in the X direction.

(87) After step **108**, each of the dielectric walls **19** has an end surface (S3) interconnecting the first and second surfaces (S1, S2), and is spaced apart from the third devices **43**. In some embodiments, as shown in FIG. **24**, the isolation feature **50** is disposed to be in direct contact with the end surface S3 of each of the dielectric walls **19**, such that in each of the device units **401**, **402**, one of the first devices **41** (which is most proximate to the isolation feature **50**) can be ensured to be isolated and/or electrically isolated from one of the second devices **42** (which is most proximate to the isolation feature **50**).

(88) In some embodiments, as shown in FIG. **25**, the isolation feature **50** has a bottom surface **50B** at a level lower than a bottom surface **25B** of each of the source/drain features **25** of the first, second and third devices **41**, **42**, **43**, so as to electrically isolate the first, second, and third devices **41**, **42**, **43** which are the most proximate to the isolation feature **50** from one another.

(89) In some embodiments, formation of the isolation feature **50** shown in FIG. **24** may include (i) forming a patterned photoresist layer on the structure obtained after step **107** to expose the gate structure **30C** shown in FIG. **20** by spin-coating followed by a lithography process, (ii) performing an etching process (through the patterned photoresist by dry etching, wet etching, other suitable processes, or combinations thereof) to remove the gate structure **30C** and the elements which are wrapped by the gate structure **30C** (i.e., corresponding ones of the channel features **182A** and portions of the dielectric walls **19**) until portions of the first, second and third fins **11**, **12**, **13** beneath the gate structure **30C** are partially removed so as to form a trench (not shown), and (ii) depositing the dielectric material for forming the gate isolation portion **51** to fill the trench, followed by a planarization process, for example, but not limited to, CMP, to remove an excess of the dielectric material for forming the gate isolation portion **51** until the ILD features **27** are exposed, thereby obtaining the isolation feature **50**. In some embodiments, the dielectric material for forming the gate isolation portion **51** is similar to that for forming the dielectric walls **19**, and thus details thereof are omitted for the sake of brevity. In some embodiments, the dielectric material of the gate isolation portion **51** may be the same as or different from that of the dielectric walls **19**. It is worth mentioning that, as shown in FIGS. **25** and **26**, portions of the first, second and third fins **11**, **12**, **13** still remain in position beneath the isolation feature **50** after step **108**, so the direct contact between one of the third fins **13** and corresponding one(s) of the first and second fins **11**, **12** can be observed after step **108**.

(90) FIGS. **27** and **28** are views similar to that of FIG. **24**, but illustrating first and second variants of the isolation feature **50** in accordance with some other embodiments.

(91) Since process variation in steps **101** and **102** may cause each of the dielectric walls **19** to have different length in the X direction, at least two gate isolation portions **51L**, **51R** are included in the isolation feature **50** to compensate for such process variation. As shown in FIGS. **27** and **28**, the isolation feature **50** includes at least two gate isolation portions **51L**, **51R** which are elongated in the Y direction and spaced apart from each other in the X direction, and which are located at two opposite sides of the end surface (**S3**) of each of the dielectric walls **19**. A proximate one of the gate isolation portions **51L** is formed to penetrate each of the dielectric walls **19**, and a distal one of the gate isolation portions **51R** is formed to be spaced apart from the end surface (**S3**) of each of the dielectric walls **19**. In some embodiments, the elements disposed between the two gate isolation portions **51L**, **51R** are dummy elements, and may be referred to as fillers.

(92) Furthermore, each of the device units **401**, **402** is spaced apart from each of the device assemblies **403**, **404**, **405** by a distance in the X direction. The distance may be adjusted by the number and/or distribution of the gate isolation portions **51** in the isolation feature **50**, and may be less than ten times the first pitch (**CPP1**) or greater than 0.1 time the first pitch (**CPP1**). For example, the isolation features **50** shown in FIGS. **27** and **28** both include two gate isolation portions **51L**, **51R** which are made by replacement of different gate structures. In details, the isolation feature **50** of the first variant shown in FIG. **27** is formed by (i) performing an etching process to remove the gate structures **30C**, **30D** and portions of elements beneath the gate structures **30C**, **30D** until portions of the first and second fins **11**, **12** beneath the gate structure **30C** are partially removed, and portions of the third fins **13** beneath the gate structure **30D** are partially removed so as to form the trenches, and (ii) filling the trenches using the dielectric material for forming the gate isolation portions **51**. The isolation feature **50** shown in FIG. **28** is formed by a manner similar to that of the first variant, except that in the etching process of the second variant, the gate structures **30B**, **30D** (rather than the gate structures **30C**, **30D**) and portions of elements beneath the gate structures **30B**, **30D** are removed. Therefore, the isolation feature **50** shown in FIG. **28** has a dimension in the X direction that is greater than a dimension of the isolation feature **50** shown in FIG. **27** in the X direction. That is, in FIG. **28**, the device assemblies **403**, **404**, **405** are spaced apart from the device units **401**, **402** by a greater distance in the X direction. Accordingly, the third devices **43** in the device assemblies **403**, **404**, **405** shown in FIG. **28** may be less affected (or disturbed) by the first and second devices **41**, **42** in the device units **401**, **402** during operation.

(93) FIG. **29** is a view similar to that of FIG. **28**, but illustrating a third variant of the isolation feature **50** in accordance with some other embodiments. The isolation feature **50** shown in FIG. **29** may be formed by a manner similar to that for forming the isolation feature **50** shown in FIG. **28** except that in the etching process of the third variant, the gate structure **30C** shown in FIG. **28** and portions of elements therebeneath are removed together with removal of the gate structures **30B**, **30D** to expose the etched portions of first, second and third fins **11**, **12**, **13**. Therefore, in the third variant, the isolation feature **50** further includes a gate isolation portion **51M** between the gate isolation portions **51L**, **51R**.

(94) Referring to FIG. **1** and the examples illustrated in FIGS. **30** and **31**, the method **100** proceeds to step **109**, where a plurality of contact features **60** and contact vias **71** are respectively formed on the source/drain features **25**, and the semiconductor structure **90** is thus formed. FIG. **30** is a view similar to that of FIG. **24**, but further illustrating the contact features **60** (two pairs of the contact features **60** and two pairs of the contact via **71** are shown). FIG. **31** is a cross-sectional view taken along lines H-H' of FIG. **30** in accordance with some embodiments but further illustrating the other elements omitted in FIG. **30**.

(95) In some embodiments, when the fourth pitch (**CPP4**) is greater than the third pitch (**CPP3**), as shown in FIG. **20**, each of the contact features **60** formed on a corresponding one of the source/drain features **25** in the device assemblies **403**, **404**, **405** may have a width (**MD2**) in the X direction that is greater than a width (**MD1**) of each of the contact features **60** formed on a corresponding one of the source/drain features **25** in the device units **401**, **402**. In some

embodiments, a ratio of the width (MD2) to the width (MD1) may range from about 1.2 to about 3. Furthermore, in some embodiments, each of the contact vias **71** disposed on a corresponding one of the contact features **60** on the source/drain features **25** in the device assemblies **403, 404, 405** may have an area (A2) that is greater than an area (A1) of each of the contact vias **71** disposed on a corresponding one of the contact features **60** on the source/drain features **25** in the device unit **401, 402**. In some embodiments, a ratio of the area (A2) to the area (A1) may range from about 1.1 to about 5. Accordingly, a relatively large current is allowed to pass through the contact features **60** and the contact vias **71** which are sequentially and respectively disposed on the source/drain features **25** in the device assemblies **403, 404, 405**.

(96) In some embodiments, step **109** includes sub-steps of: (i) forming a patterned mask (not shown) on the structure obtained after step **108**; (ii) performing an etching process (for example, but not limited to, dry etching, wet etching, or a combination thereof) through the patterned mask layer to form openings (not shown), each extending through a corresponding one of the ILD features **27** and a corresponding one of the contact etching stop features **26** shown in FIG. **25** to expose a corresponding one of the source/drain features **25**; (iii) filling a conductive material for forming the contact features **60** in the openings using for example, but not limited to, ALD, CVD, plating, or other suitable techniques; (iv) removing an excess of the conductive material for forming the contact features **60** to expose the self-aligned dielectric features **33** and the isolation feature **50** using CMP or other suitable techniques to form the contact features **60**; (v) forming an inter-metal dielectric (IMD) layer **70** on the structure after formation of the contact features **60**; and (vi) forming the contact vias **71** in the IMD layer **70** in a manner similar to sub-steps (i) to (iv) for forming the contact features **60**, such that the contact vias **71** is electrically connected to the contact features **60**, respectively.

(97) In some embodiments, the conductive material for forming each of the contact features **60** and the contact vias **71** may include, for example, but not limited to, W, Al, Ru, cobalt (Co), copper (Cu), palladium (Pd), nickel (Ni), platinum (Pt), a low resistivity metal constituent, or the like, or combinations thereof. In some embodiments, the IMD layer **70** may be made of a dielectric material similar to the dielectric material for forming the ILD feature **27**, and thus details thereof are omitted for the sake of brevity. Other suitable materials and/or processes for forming the contact features **60** and the contact vias **71** are within the contemplated scope of the present disclosure. For example, in some embodiments, a metal silicide feature (not shown) is formed between each of the source/drain features **25** and a corresponding one of the contact features **60** for reducing a contact resistance (R_{csd}) between each of the source/drain features **25** and the corresponding contact feature **60**. In some embodiments, the metal silicide feature may include titanium silicide, ruthenium silicide, nickel silicide, cobalt silicide, molybdenum silicide, or combinations thereof. Other suitable materials for the metal silicide are within the contemplated scope of the present disclosure.

(98) In some embodiments, the semiconductor structure **90** may further include a plurality of interconnect layers each including an IMD feature (not shown) in which electrically conductive elements (not shown, for example, metal contacts, metal lines and/or metal vias) are formed so as to permit the devices **41, 42, 43** to be electrically connected to external circuits through the electrically conductive elements. In some embodiments, the interconnect layers may be formed by a dual damascene process, a single damascene process, or other suitable back-end-of-line (BEOL) techniques.

(99) In some embodiments, some steps in the method **100** may be modified, replaced, or eliminated without departure from the spirit and scope of the present disclosure. For example, as shown in FIG. **32**, each of the real gate portions **301, 302, 303, 304** in the gate structure **30A** may be spaced apart from each other by a corresponding one of isolation sections **80** according to application requirement. Each of the isolation sections **80** may be made of a dielectric material to similar the dielectric material of the gate isolation portion **51**, and is independently positioned on a

corresponding one of the dielectric walls **19** or a corresponding one of the isolation regions **17**. In some embodiments, as shown in FIG. **32**, the isolation sections **80** may be formed after formation of the gate structures **30** and before formation of the self-aligned dielectric features **33**. In some other not shown embodiments, the isolation sections **80** may be formed after step **107** (i.e., the replacement gate process) and before step **109** (i.e., formation of the contact features **60** and the contact vias **71**). In some not shown embodiments, step **108** (i.e., formation of the isolation feature **50**) may be performed after step **106** (i.e., formation of the contact etching stop features **26** and the ILD features **27**) and before step **107** (i.e., the replacement gate process). In this case, formation of the isolation feature **50** may include removing at least one of the dummy gate portions **20** and portions of elements therebeneath in a way similar to the etching process for removing the gate structure **30C** in step **107** to form at least one trench, followed by filling the dielectric material for forming at least one gate isolation portion **51** therein.

(100) In some embodiments, each of the device units **401**, **402** may have a forksheet transistor architecture, and each of the device assemblies **403**, **404**, **405** may have a GAA transistor architecture.

(101) The connection relationship between one of the device units and corresponding one(s) of the device assemblies is described above through the semiconductor structure **90**. In the following, four device layouts **91**, **92**, **93**, **94** applied to inverters are exemplified according to the design spirit of the semiconductor structure **90**. Similar numerals from the above-mentioned embodiments have been used where appropriate, with some construction differences being indicated with different numerals.

(102) FIG. **33** is a schematic view illustrating a first device layout **91** in accordance with some embodiments. The first device layout **91** includes a plurality of the device units **401** periodically arranged to form an array, a plurality of the device assemblies **403** integrated in the array of the device units **401**, and a plurality of the isolation features **50** elongated in the Y direction and spaced apart from each other in the X direction, so that each of the isolation features **50** can electrically isolate any two adjacent ones of the device units **401**, and can electrically isolate one of the device units **401** from an adjacent one of the device assemblies **403**.

(103) In practical, each of the device units **401** may include a plurality of the first devices **41** disposed on the first fin **11** and a plurality of the second devices **42** disposed on the second fin **12**, and each of the device assemblies **403** may include a plurality of the third devices **43** disposed on the third fin **13**. In FIG. **33**, for the purposes of simplicity and clarity, a single first device **41** and a single second device **42** are shown in each of the device units **401**, and a single third device **43** is shown in each of the device assemblies **403**. Furthermore, it is noted that the elements (e.g., the source/drain features, the real gate portions, etc.) of each of the devices **41**, **42**, **43** are omitted in FIG. **33** for the purposes of simplicity and clarity. In FIG. **33**, the devices **41**, **42** serving as n-FETs are denoted by “N,” the devices **41**, **42** serving as p-FETs are denoted by “P,” and the devices **43** serving as p-FETs are denoted by “PP.” The third device **43** has a channel width in the Y direction which is much greater than that of each of the first and second devices **41**, **42**.

(104) In the first device layout **91**, the third fin **13** of each of the device assemblies **403** has a first surface (S4) and a second surface (S5) which are opposite to each other in the X direction. The first surface (S4) of the third fin **13** of one of the device assemblies **403** is in direct contact with the first and second fins **11**, **12** of a corresponding one of the device units **401**, and the second surface (S5) of the third fin **13** of the one of the device assemblies **403** is in direct contact with the first and second fins **11**, **12** of another corresponding one of the device units **401**.

(105) It can be seen that a plurality of basic inverter units **9A** and a plurality of first advanced inverter units **9B** are regularly arranged in the first device layout **91**. In the case that in each of the device units **401**, the first and second devices **41**, **42** have the same type of conductivity, each of the basic inverter units **9A** includes an n-FET of one of the device units **401** and a p-FET of a most adjacent one of the device units **401**, and may be referred to as a PN inverter. Each of the first

advanced inverter units **9B** includes (i) a p-FET of one of the device assemblies **403** and (ii) two n-FETs of two most adjacent ones of the device units **401** which are most adjacent to the p-FET of the one of the device assemblies **403** in the Y direction, and may be referred to as an NPN inverter (or an NPPN inverter). In some not shown embodiments, when an n-FET is disposed on one of the device assemblies **403** and two p-FETs are respectively disposed on two most adjacent ones of the device units **401**, a PNP inverter (or a PNNP inverter) may be obtained.

(106) Each of the first advanced inverter units **9B** has a cell height (H2) which may be two times a cell height (H1) of each of the basic inverter units **9A**. The first advanced inverter units **9B** have a device performance (e.g., speed) better than that of the basic inverter units **9A** owing to a relatively large channel width of the third device **43** in each of the first advanced inverter units **9B**. In some embodiments, as shown in FIG. **33**, the two n-FETs in each of the first advanced inverter units **9B** may have a channel width in the Y direction which is greater than that of the n-FET in the basic inverter unit **9A** for further improving the device performance thereof.

(107) FIG. **34** is a schematic view illustrating a second device layout **92** in accordance with some embodiments. FIG. **34** is a view similar to that of FIG. **33** except that the device assemblies **403** in the second device layout **92** are integrated in the array of the device unit **401** in a different manner.

(108) Similar to the layout shown in FIG. **33**, in FIG. **34**, the first surface (S4) of the third fin **13** of one of the device assemblies **403** is in direct contact with the first and second fins **11**, **12** of a corresponding one of the device units **401**, and the second surface (S5) of the third fin **13** of the one of the device assemblies **403** is in direct contact with the first and second fins **11**, **12** of another corresponding one of the device units **401**. The difference between the layouts shown in FIGS. **33** and **34** is that two of the device assemblies **403**, having opposite types of conductivity, are arranged adjacent to each other without the device units **401** being disposed therebetween. One of the third devices **43** shown in FIG. **34** serving as an n-FET is denoted by “NN,” and the third devices **43** each has a channel width in the Y direction which is much greater than that of each of the first and second devices **41**, **42**.

(109) In some embodiments, a plurality of second advanced inverter units **9C** (one of which is shown in FIG. **34**) may be regularly arranged in the array of the basic inverter units **9A**.

(110) The second advanced inverter unit **9C** includes (i) a p-FET of one of the device assemblies **403** (hereinafter referred to as “9CPP FET”), (ii) an n-FET of an adjacent one of the device assemblies **403** (hereinafter referred to as “9CNN FET”) which is most adjacent to the 9CPP FET in the Y direction, (iii) one of n-FETs of a first adjacent one of the device units **401** (hereinafter referred to as “9CN FET”) which is most adjacent to the 9CNN FET in the Y direction, and (iv) one of p-FETs of a second adjacent one of the device units **401** (hereinafter referred to as “9CP FET”) which is most adjacent to the n-FET of 9CNN in the Y direction, and may be referred to as a PPNN inverter. In some embodiments, in the second advanced inverter unit **9C**, the 9CN FET and the 9CP FET may be dummy FETs.

(111) The second advanced inverter unit **9C** has a cell height (H3) which may be three times a cell height (H1) of each of the basic inverter units **9A**. The second advanced inverter unit **9C** has an improved performance (e.g., speed) than that of the basic inverter units **9A** owing to a relatively large channel width of each of the third devices **43** in the second advanced inverter units **9C**. In some embodiments, as shown in FIG. **34**, in the second advanced inverter unit **9C**, when the 9CN FET and the 9CP FET are dummy FETs, channel widths of the 9CN FET and the 9CP FET in the Y direction may be substantially equal to channel widths of the n-FET and the p-FET of the basic inverter units **9A**, respectively.

(112) In some not shown embodiments, a variation of the second advanced inverter unit includes a 9CN FET, a 9CPP FET, a 9CNN FET, a 9CPP FET, a 9CNN FET and a 9CP FET, which are arranged in the Y direction in this order. In this case, the variation of the second advanced inverter unit includes two PPNN inverters, and has a cell height which may be five times a cell height (H1) of each of the basic inverter units **9A**.

(113) FIG. 35 is a schematic view illustrating a third device layout 93 in accordance with some embodiments. FIG. 35 is a view similar to that of FIG. 33 except that the third device layout 93 includes three of the device assemblies 403, 404, 405 which are arranged adjacent to one another and which are arranged to connect with four of the device units 401 in the array of the device units 401. A plurality of the isolation features 50 are disposed to electrically isolate any two adjacent ones of the device units 401, and to electrically isolate one of the device units 401 from an adjacent one of the device assemblies 403, 404, 405.

(114) As shown in FIG. 35, one of the third devices 43 disposed on the main fin 130 serves as a p-FET, and is denoted by "PP," and the one of the third devices 43 disposed on the main fin 130 has a channel width in the Y direction which is much greater than that of each of the first and second devices 41, 42. The other two of the third devices 43 which are respectively disposed on the first and second auxiliary fins 131, 132 serve as n-FETs, and are denoted by "N." The other two of the third devices 43 each has a channel width in the Y direction which is greater than that of each of the first and second devices 41, 42 and which is smaller than that of the third device 43 disposed on the main fin 130.

(115) In the third device layout 93, each of the main fin 130 and the first and second auxiliary fins 131, 132 has a first surface (S6, S8, S10) and a second surface (S7, S9, S11) which are opposite to each other in the X direction. The first surface (S6) of the main fin 130 of the device assembly 403 is in direct contact with the second fin 12 of the first pair 1A and the first fin 11 of the second pair 1B. The second surface (S7) of the main fin 130 is in direct contact with the second fin 12 of a third pair 1C and the first fin 11 of a fourth pair 1D. The first surface (S8) of the first auxiliary fin 131 of the device assembly 404 is in direct contact with the first fin 11 of the first pair 1A, and the second surface (S9) of the first auxiliary fin 131 is in direct contact with the first fin 11 of the third pair 1C. The first surface (S10) of the second auxiliary fin 132 of the device assembly 405 is in direct contact with the second fin 12 of the second pair 1B, and the second surface (S11) of the second auxiliary fin 132 is in direct contact with the second fin 12 of the fourth pair 1D.

(116) In some embodiments, as shown in FIG. 35, in each of the device units 401, the first and second devices 41, 42 have opposite types of conductivity, and a plurality of third advanced inverter units 9D (one of which is shown in FIG. 35) may be regularly arranged in the array of the basic inverter units 9A.

(117) Each of the basic inverter units 9A includes an n-FET and a p-FET in the same one of the device units 401, and may be referred to as a PN inverter. The third advanced inverter unit 9D includes a p-FET in the device assembly 403, and two n-FETs respectively in the device assemblies 404, 405, and may be referred to as an NPN inverter (or an NPPN inverter). In some not shown embodiments, when an n-FET is disposed on the device assembly 403 and two p-FETs are respectively disposed on the device assemblies 404, 405, a PNP inverter (or a PNNP inverter) may be obtained.

(118) The third advanced inverter unit 9D has a cell height (H4) which may be two times a cell height (H1) of each of the basic inverter units 9A. The third advanced inverter unit 9D has a device performance (e.g., speed) better than that of the basic inverter units 9A owing to a relatively large channel width of at least one of the third devices 43 in the third advanced inverter unit 9D.

(119) FIG. 36 is a schematic view illustrating a fourth device layout 94 in accordance with some embodiments. FIG. 36 is a view similar to that of FIG. 35 except that the fourth device layout 94 includes four of the device assemblies 403, 404, 405 which are arranged adjacent to one another and which are arranged to connect with six of the device units 401 in the array of the device units 401. The two device assemblies 403 are disposed between the device assemblies 404, 405. As shown in FIG. 36, the third device 43 disposed on the main fin 130 of one of the device assemblies 403 serves as an n-FET, and is denoted by "NN," while the third device 43 disposed on the second auxiliary fin 132 serves as a p-FET, and is denoted by "P."

(120) In some embodiments, as shown in FIG. 36, a plurality of fourth advanced inverter units 9E

(one of which is shown in FIG. 36) may be regularly arranged in the array of the basic inverter units **9A**.

(121) The fourth advanced inverter unit **9E** includes a p-FET of one of the device assemblies **403** (hereinafter referred to as “9EPP FET”), an n-FET of an adjacent one of the device assemblies **403** (hereinafter referred to as “9ENN FET”), an n-FET of the device assembly **404** (hereinafter referred to as “9EN FET”), and a p-FET of the device assembly **405** (hereinafter referred to as “9EP FET”), and may be referred to as a PPNN inverter. In some embodiments, the 9EN FET and the 9EP FET may be dummy FETs.

(122) The fourth advanced inverter units **9E** has a cell height (H5) which may be three times a cell height (H1) of each of the basic inverter units **9A**. The fourth advanced inverter units **9E** has an improved device performance (e.g., speed) than that of the basic inverter units **9A** owing to a relatively large channel width of at least two of the third devices **43** of the device assemblies **403** in the fourth advanced inverter units **9E**. In some embodiments, as shown in FIG. 36, when the 9EN FET and the 9EP FET are dummy FETs, channel widths of the 9EN FET and the 9EP FET in the Y direction may be substantially equal to channel widths of the n-FET and the p-FET of the basic inverter unit **9A**, respectively.

(123) In some not shown embodiments, a variation of the fourth advanced inverter unit includes a 9EN FET, a 9EPP FET, a 9ENN FET, a 9EPP FET, a 9ENN FET, and a 9EP FET, which are arranged in the Y direction in such order. In this case, the variation of the fourth advanced inverter unit may include two PPNN inverters, and has a cell height which may be five times a cell height (H1) of each of the basic inverter units **9A**.

(124) In the semiconductor structure of this disclosure, the fins of at least one device unit (which includes a plurality of basic devices, i.e., the first and second devices) and at least one device assembly (which includes at least one high performance device, i.e., the third device(s)) are directly connected to each other. By arrangement between at least one isolation feature and the dielectric wall of the at least one device unit in the semiconductor structure, a plurality of the basic devices and a plurality of the high performance devices can be electrically isolated from one another while being integrated together with a high integration density. Furthermore, taking the inverter as an example, since a cell height of the high performance inverter unit is an integral multiple of a cell height of each of the basic inverter units, the high performance inverter unit may be easily arranged in an array of the basic inverter units. Therefore, the semiconductor structure of this disclosure has a good integration compatibility, and provides a flexible strategy capable of integrating high performance devices into an existing device layout.

(125) In accordance with some embodiments of the present disclosure, a semiconductor structure includes: a substrate, a first fin, a second fin, a third fin, a dielectric wall, and an isolation feature which are disposed on the substrate; and a first device, a second device and at least one third device which are respectively disposed on the first, second and third fins. The first and second fins are spaced apart from each other. The third fin is disposed to be in direct contact with at least one of the first and second fins. The dielectric wall has a first wall surface and a second wall surface. The first device includes a plurality of first channel features which extend away from the first wall surface and which are spaced apart from each other, and two first source/drain features spaced apart from each other such that each of the first channel features interconnects the first source/drain features. The second device includes a plurality of second channel features which extend away from the second wall surface and which are spaced apart from each other, and two second source/drain features spaced apart from each other such that each of the second channel features interconnects the second source/drain features. The at least one third device includes a plurality of third channel features which are spaced apart from each other, and two third source/drain features spaced apart from each other such that each of the third channel features interconnects the third source/drain features. The isolation feature is disposed to permit the third device to be electrically isolated from the first and second devices.

(126) In accordance with some embodiments of the present disclosure, the first and second fins are spaced apart from each other in a Y direction, and are elongated in an X direction transverse to the Y direction. The first and second wall surfaces are opposite to each other in the Y direction. The first channel features are spaced apart from each other in a Z direction transverse to both the X and Y directions, and each of the first channel features extends from the first wall surface in the Y direction by a first channel width. The second channel features are spaced apart from each other in the Z direction, and each of the second channel features extends from the second wall surface in the Y direction by a second channel width. The third channel features are spaced apart from each other in the Z direction, and each of the third channel features has a third channel width in the Y direction. The third channel width is greater than each of the first and second channel widths.

(127) In accordance with some embodiments of the present disclosure, the semiconductor structure further includes a first real gate portion, a second real gate portion and a third real gate portion. The first real gate portion is disposed around the first channel features, and the second real gate portion is disposed around the second channel features. The first and second real gate portions extend toward each other in the Y direction to merge on the dielectric wall such that the two first source/drain features are respectively located at two opposite sides of the first real gate portion in the X direction, and such that the two second source/drain features are respectively located at two opposite sides of the second real gate portion in the X direction. The third real gate portion is spaced apart from the first real gate portion in the X direction, and is elongated in the Y direction. The third real gate portion is disposed to surround the third channel features, and has a gate width in the X direction which is greater than a gate width of each of the first and second real gate portions in the X direction.

(128) In accordance with some embodiments of the present disclosure, the isolation feature is spaced apart from each of the first, second and third real gate portions in the X direction. The dielectric wall has an end surface interconnecting the first and second wall surfaces, and is spaced apart from the third device. The isolation feature includes a gate isolation portion which is made of a dielectric material, and which is elongated in the Y direction. The gate isolation portion is being disposed to be in direct contact with the end surface of the dielectric wall, such that the first and second devices are isolated from each other.

(129) In accordance with some embodiments of the present disclosure, the isolation feature is spaced apart from each of the first, second and third real gate portions in the X direction. The dielectric wall has an end surface interconnecting the first and second wall surfaces. The isolation feature includes two gate isolation portions which are elongated in the Y direction, which are spaced apart from each other in the X direction, and which are disposed at two opposite sides of the end surface of the dielectric wall. A proximate one of the gate isolation portions is disposed to penetrate the dielectric wall, and a distal one of the gate isolation portions is disposed to be spaced apart from the end surface of the dielectric wall.

(130) In accordance with some embodiments of the present disclosure, the isolation feature has a bottom surface at a level lower than a bottom surface of each of the first, second and third source/drain features, so as to electrically isolate the first, second and third devices from one another.

(131) In accordance with some embodiments of the present disclosure, the third fin is in direct contact with both of the first and second fins. The isolation feature is disposed to elongate in the Y direction such that the third device is separated from the first and second devices by the isolation feature.

(132) In accordance with some embodiments of the present disclosure, the third fin is in direct contact with the second fin. The semiconductor structure further includes a fourth fin disposed on the substrate, a fourth device disposed on the fourth fin, a first real gate portion, a second real gate portion, a third real gate portion, and a fourth real gate portion. The fourth fin is spaced apart from the third fin in the Y direction, and is elongated in the X direction to be in contact with the first fin.

The fourth device includes a plurality of fourth channel features which are spaced apart from each other in the Z direction, and two fourth source/drain features spaced apart from each other in the X direction such that each of the fourth channel features interconnects the fourth source/drain features. The first real gate portion is disposed around the first channel features, and the second real gate portion is disposed around the second channel features. The first and second real gate portions extend toward each other in the Y direction to merge on the dielectric wall such that the two first source/drain features are respectively located at two opposite sides of the first real gate portion in the X direction, and such that the two second source/drain features are respectively located at two opposite sides of the second real gate portion in the X direction. The third real gate portion and the fourth real gate portion are spaced apart from the first and second real gate portions in the X direction. The third real gate portion is disposed to surround the third channel features, and the fourth real gate portion is disposed to surround the fourth channel features. The third and fourth real gate portions extend toward each other in the Y direction to merge together such that the two third source/drain features are respectively located at two opposite sides of the third real gate portion in the X direction, and such that the two fourth source/drain features are respectively located at two opposite sides of the fourth real gate portion in the X direction.

(133) In accordance with some embodiments of the present disclosure, a semiconductor structure includes a substrate, at least one device unit, at least one device assembly and an isolation feature which are disposed on the substrate. The at least one device unit includes a first fin and a second fin which are spaced apart from each other in a Y direction, a dielectric wall which has a first wall surface and a second wall surface opposite to the first wall surface, and a first device and a second device which are respectively disposed on the first and second fins. Each of the first and second devices includes a plurality of channel features which extend away from a corresponding one of the first and second wall surface to be disposed over a corresponding one of the first and second fins so as to permit the channel features to be spaced apart from each other in a Z direction transverse to the Y direction, and two source/drain features which are disposed on a corresponding one of the first and second fins, and which are spaced apart from each other in an X direction transverse to the Y and Z directions such that each of the channel features interconnects the two source/drain features. The at least one device assembly includes a third fin which is in direct contact with at least one of the first and second fin, and a third device which is disposed on the third fin. The third device includes a plurality of channel features spaced apart from each other in the Z direction, and two source/drain features disposed on the third fin and spaced apart from each other in the X direction such that each of the channel features interconnects the two source/drain features. The isolation feature extends in the Y direction through the first and second fins of the at least one device unit and through the third fin of the at least one device assembly so as to permit the third device to be electrically isolated from the first and second devices.

(134) In accordance with some embodiments of the present disclosure, the semiconductor structure includes two of the device units which are spaced apart in the Y direction. The third fin of the at least one device assembly is in direct contact with the second fin of a first one of the device units and the first fin of a second one of the device units. The isolation feature extends in the Y direction through the first and second fins of the device units and through the third fin of the at least one device assembly.

(135) In accordance with some embodiments of the present disclosure, the semiconductor structure includes two of the device units which are spaced apart in the Y direction, and three of the device assemblies which are spaced apart in the Y direction. The third fin of a middle one of the device assemblies is in direct contact with the second fin of a first one of the device units and the first fin of a second one of the device units. The second fin of the first one of the device units is disposed to confront the first fin of the second one of the device units in the Y direction. A first one of the device assemblies and a second one of the device assemblies are disposed at two opposite sides of the middle one of the device assemblies in the Y direction. The third fin of the first one of the

device assemblies is in direct contact with the first fin of the first one of the device units. The third fin of the second one of the device assemblies is in direct contact with the second fin of the second one of the device units. The isolation feature extends in the Y direction through the first and second fins of the device units and through the third fins of the device assemblies.

(136) In accordance with some embodiments of the present disclosure, each of the channel features of the middle one of the device assemblies has a channel width in the Y direction which is greater than a channel width of each of the channel features of each of the device units in the Y direction.

(137) In accordance with some embodiments of the present disclosure, each of the channel features of the middle one of the device assemblies has a channel width in the Y direction which is greater than the channel width of each of the channel features of the first and second ones of the device assemblies in the Y direction.

(138) In accordance with some embodiments of the present disclosure, the source/drain features of the middle one of the device assemblies have a conductivity type different from a conductivity type of the source/drain features of the first and second ones of the device assemblies.

(139) In accordance with some embodiments of the present disclosure, a method for manufacturing a semiconductor structure includes forming a patterned structure, forming a dielectric wall, forming a first device, a second device and a third device, and forming an isolation feature. The patterned structure is formed on a substrate. The patterned structure includes a first fin, a second fin and a third fin disposed on the substrate. The first and second fins are elongated in an X direction, and are spaced apart from each other in a Y direction transverse to the X direction. The third fin is in direct contact with at least one of the first and second fins. The dielectric wall is formed on the substrate, and has a first wall surface and a second wall surface. The first, second and third devices are respectively formed on the first, second and third fins. The first device includes a plurality of first channel features which extend away from the first wall surface and which are spaced apart from each other in a Z direction transverse to the X and Y directions, a first real gate portion which is disposed around the first channel features, and two first source/drain features which are located at two opposite sides of the first real gate portion to be spaced apart from each other in the X direction such that each of the first channel features interconnects the first source/drain features. The second device includes a plurality of second channel features which extend away from the second wall surface and which are spaced apart from each other in the Z direction, a second real gate portion which is disposed around the second channel features, and two second source/drain features which are located at two opposite sides of the second real gate portion to be spaced apart from each other in the X direction such that each of the second channel features interconnects the second source/drain features. The third device includes a plurality of third channel features which are spaced apart from each other in the Z direction, a third real gate portion which is disposed around the third channel features, and two third source/drain features which are located at two opposite sides of the third real gate portion to be spaced apart from each other in the X direction such that each of the third channel features interconnects the third source/drain features. The isolation feature is formed on the substrate. The isolation feature extends in the Y direction through the first, second and third fins to permit the third device to be electrically isolated from the first and second devices.

(140) In accordance with some embodiments of the present disclosure, the third fin has a fin width in the Y direction which is greater than a fin width of each of the first and second fins in the Y direction.

(141) In accordance with some embodiments of the present disclosure, the dielectric wall has an end surface interconnecting the first and second wall surfaces, and the isolation feature includes a gate isolation portion. Forming the first, second and third devices includes (i) forming a first dummy gate portion disposed over the first and second fins and the dielectric wall, a second dummy gate portion disposed over the first, second and third fins, and a third dummy gate portion disposed over the third fin, the first, second and third dummy gate portions being spaced apart from each other in the X direction, and (ii) performing a replacement gate process such that the first

dummy gate portion is replaced with a first gate structure including the first and second real gate portions, the second dummy gate portion is replaced with a second gate structure, and the third dummy gate portion is replaced with a third gate structure including the third real gate portion. Forming the isolation feature includes (i) performing an etching process until the second gate structure is removed and portions of the first, second and third fins beneath the second gate structure are partially removed so as to form a trench which has a bottom at a level lower than a bottom surface of each of the first, second, and third source/drain features, and (ii) filling a dielectric material into the trench so as to form the gate isolation portion which is in direct contact with the end surface of the dielectric wall.

(142) In accordance with some embodiments of the present disclosure, the dielectric wall has an end surface interconnecting the first and second wall surfaces, and the isolation feature includes a gate isolation portion. Forming the first, second and third devices and the isolation feature includes (i) forming a first dummy gate portion disposed over the first and second fins, a second dummy gate portion disposed over the first, second and third fins, and a third dummy gate portion disposed over the third fin, the first, second and third dummy gate portions being spaced apart from each other in the X direction, (ii) performing an etching process until the second dummy gate portion and portions of the first, second and third fins beneath the second dummy gate portion are partially removed so as to form a trench having a bottom at a level lower than a bottom surface of each of the first, second, and third source/drain features, (iii) filling a dielectric material into the trench so as to form the gate isolation portion which is in direct contact with the end surface of the dielectric wall, and (iv) performing a replacement gate process such that the first dummy gate portion is replaced with a first gate structure including the first and second real gate portions, and the third dummy gate portion is replaced with a second gate structure including the third real gate portion.

(143) In accordance with some embodiments of the present disclosure, the dielectric wall has an end surface interconnecting the first and second wall surfaces, and the isolation feature includes two gate isolation portions. Forming the first, second and third devices includes (i) forming first and second dummy gate portions disposed over the first and second fins and the dielectric wall, and third and fourth dummy gate portions disposed over the third fin, the first, second, third and fourth dummy gate portions being spaced apart from each other in the X direction, the second and third dummy gate portions being disposed between the first and fourth dummy gate portions, and (ii) performing a replacement gate process such that the first dummy gate portion is replaced with a first gate structure including the first and second real gate portions, the second and third dummy gate portions are respectively replaced with second and third gate structures, and the fourth dummy gate portion is replaced with a fourth gate structure including the third real gate portion. Forming the isolation feature includes (i) performing an etching process until the second and third gate structures are removed, portions of the first and second fins beneath the second gate structure are partially removed, and a portion of the third fin beneath the third gate structure is partially removed so as to form two trenches each having a bottom at a level lower than a bottom surface of each of the first, second, and third source/drain features, and (ii) filling a dielectric material into the trenches so as to respectively form the two gate isolation portions which are located at two opposite sides of the end surface of the dielectric wall.

(144) In accordance with some embodiments of the present disclosure, the isolation feature has a bottom surface at a level lower than a bottom surface of each of the first, second, and third source/drain features.

(145) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes or structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may

make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A semiconductor structure comprising: a substrate; a first fin and a second fin which are disposed on the substrate, and which are spaced apart from each other; a dielectric wall disposed on the substrate, and having a first wall surface and a second wall surface; a third fin disposed on the substrate to be in direct contact with at least one of the first and second fins; a first device disposed on the first fin and including a plurality of first channel features which extend away from the first wall surface and which are spaced apart from each other, and two first source/drain features spaced apart from each other such that each of the first channel features interconnects the first source/drain features; a second device disposed on the second fin and including a plurality of second channel features which extend away from the second wall surface and which are spaced apart from each other, and two second source/drain features spaced apart from each other such that each of the second channel features interconnects the second source/drain features; at least one third device disposed on the third fin and including a plurality of third channel features which are spaced apart from each other, and two third source/drain features spaced apart from each other such that each of the third channel features interconnects the third source/drain features; and an isolation feature disposed on the substrate to permit the third device to be electrically isolated from the first and second devices.
2. The semiconductor structure of claim 1, wherein: the first and second fins are spaced apart from each other in a Y direction, and are elongated in an X direction transverse to the Y direction; the first and second wall surfaces are opposite to each other in the Y direction; the first channel features are spaced apart from each other in a Z direction transverse to both the X and Y directions, each of the first channel features extending from the first wall surface in the Y direction by a first channel width; the second channel features are spaced apart from each other in the Z direction, each of the second channel features extending from the second wall surface in the Y direction by a second channel width; the third channel features are spaced apart from each other in the Z direction, each of the third channel features having a third channel width in the Y direction; and the third channel width is greater than each of the first and second channel widths.
3. The semiconductor structure of claim 2, further comprising: a first real gate portion and a second real gate portion, the first real gate portion being disposed around the first channel features, the second real gate portion being disposed around the second channel features, the first and second real gate portions extending toward each other in the Y direction to merge on the dielectric wall such that the two first source/drain features are respectively located at two opposite sides of the first real gate portion in the X direction, and such that the two second source/drain features are respectively located at two opposite sides of the second real gate portion in the X direction; and a third real gate portion spaced apart from the first real gate portion in the X direction and elongated in the Y direction, the third real gate portion being disposed to surround the third channel features, the third real gate portion having a gate width in the X direction which is greater than a gate width of each of the first and second real gate portions in the X direction.
4. The semiconductor structure of claim 3, wherein: the isolation feature is spaced apart from each of the first, second and third real gate portions in the X direction; the dielectric wall has an end surface interconnecting the first and second wall surfaces, and is spaced apart from the third device; the isolation feature includes a gate isolation portion made of a dielectric material, and is elongated in the Y direction, the gate isolation portion being disposed to be in direct contact with the end surface of the dielectric wall, such that the first and second devices are isolated from each other.
5. The semiconductor structure of claim 3, wherein: the isolation feature is spaced apart from each of the first, second and third real gate portions in the X direction; the dielectric wall has an end

surface interconnecting the first and second wall surfaces; the isolation feature includes two gate isolation portions which are elongated in the Y direction, which are spaced apart from each other in the X direction, and which are located at two opposite sides of the end surface of the dielectric wall, a proximate one of the gate isolation portions being disposed to penetrate the dielectric wall, a distal one of the gate isolation portions being disposed to be spaced apart from the end surface of the dielectric wall.

6. The semiconductor structure of claim 1, wherein the isolation feature has a bottom surface at a level lower than a bottom surface of each of the first, second and third source/drain features, so as to electrically isolate the first, second and third devices from one another.

7. The semiconductor structure of claim 2, wherein: the third fin is in direct contact with both of the first and second fins; and the isolation feature is disposed to elongate in the Y direction such that the third device is separated from the first and second devices by the isolation feature.

8. The semiconductor structure of claim 2, wherein the third fin is in direct contact with the second fin, the semiconductor structure further comprising: a fourth fin disposed on the substrate and spaced apart from the third fin in the Y direction, the fourth fin being elongated in the X direction to be in contact with the first fin; a fourth device disposed on the fourth fin and including a plurality of fourth channel features which are spaced apart from each other in the Z direction, and two fourth source/drain features spaced apart from each other in the X direction such that each of the fourth channel features interconnects the fourth source/drain features; a first real gate portion and a second real gate portion, the first real gate portion being disposed around the first channel features, the second real gate portion being disposed around the second channel features, the first and second real gate portions extending toward each other in the Y direction to merge on the dielectric wall such that the two first source/drain features are respectively located at two opposite sides of the first real gate portion in the X direction, and such that the two second source/drain features are respectively located at two opposite sides of the second real gate portion in the X direction; and a third real gate portion and a fourth real gate portion which are spaced apart from the first and second real gate portions in the X direction, the third real gate portion being disposed to surround the third channel features, the fourth real gate portion being disposed to surround the fourth channel features, the third and fourth real gate portions extending toward each other in the Y direction to merge together such that the two third source/drain features are respectively located at two opposite sides of the third real gate portion in the X direction, and such that the two fourth source/drain features are respectively located at two opposite sides of the fourth real gate portion in the X direction.

9. A semiconductor structure, comprising: a substrate; at least one device unit disposed on the substrate, and including a first fin and a second fin which are spaced apart from each other in a Y direction, a dielectric wall which has a first wall surface and a second wall surface opposite to the first wall surface, and a first device and a second device which are respectively disposed on the first and second fins, each of the first and second devices including a plurality of channel features which extend away from a corresponding one of the first and second wall surface to be disposed over a corresponding one of the first and second fins so as to permit the channel features to be spaced apart from each other in a Z direction transverse to the Y direction, and two source/drain features which are disposed on a corresponding one of the first and second fins, and which are spaced apart from each other in an X direction transverse to the Y and Z directions such that each of the channel features interconnects the two source/drain features; at least one device assembly disposed on the substrate, and including a third fin which is in direct contact with at least one of the first and second fin, and a third device which is disposed on the third fin, and including a plurality of channel features spaced apart from each other in the Z direction, and two source/drain features disposed on the third fin and spaced apart from each other in the X direction such that each of the channel features interconnects the two source/drain features; and an isolation feature disposed on the substrate and extending in the Y direction through the first and second fins of the at least one

device unit and through the third fin of the at least one device assembly so as to permit the third device to be electrically isolated from the first and second devices.

10. The semiconductor structure of claim 9, wherein: the semiconductor structure comprises two of the device units which are spaced apart in the Y direction; the third fin of the at least one device assembly is in direct contact with the second fin of a first one of the device units and the first fin of a second one of the device units; and the isolation feature extends in the Y direction through the first and second fins of the device units and through the third fin of the at least one device assembly.

11. The semiconductor structure of claim 9, wherein: the semiconductor structure comprises two of the device units which are spaced apart in the Y direction, and three of the device assemblies which are spaced apart in the Y direction; the third fin of a middle one of the device assemblies is in direct contact with the second fin of a first one of the device units and the first fin of a second one of the device units; the second fin of the first one of the device units is disposed to confront the first fin of the second one of the device units in the Y direction; a first one of the device assemblies and a second one of the device assemblies are disposed at two opposite sides of the middle one of the device assemblies in the Y direction; the third fin of the first one of the device assemblies is in direct contact with the first fin of the first one of the device units; the third fin of the second one of the device assemblies is in direct contact with the second fin of the second one of the device units; and the isolation feature extends in the Y direction through the first and second fins of the device units and through the third fins of the device assemblies.

12. The semiconductor structure of claim 11, wherein each of the channel features of the middle one of the device assemblies has a channel width in the Y direction which is greater than a channel width of each of the channel features of each of the device units in the Y direction.

13. The semiconductor structure of claim 10, wherein each of the channel features of the middle one of the device assemblies has a channel width in the Y direction which is greater than the channel width of each of the channel features of the first and second ones of the device assemblies in the Y direction.

14. The semiconductor structure of claim 10, wherein the source/drain features of the middle one of the device assemblies have a conductivity type different from a conductivity type of the source/drain features of the first and second ones of the device assemblies.

15. A method for manufacturing a semiconductor structure, comprising: forming a patterned structure on a substrate, the patterned structure including a first fin, a second fin and a third fin disposed on the substrate, the first and second fins being elongated in an X direction and spaced apart from each other in a Y direction transverse to the X direction, the third fin being in direct contact with at least one of the first and second fins; forming a dielectric wall on the substrate, the dielectric wall having a first wall surface and a second wall surface; forming a first device, a second device and a third device respectively on the first, second and third fins, the first device including a plurality of first channel features which extend away from the first wall surface and which are spaced apart from each other in a Z direction transverse to the X and Y directions, a first real gate portion which is disposed around the first channel features, and two first source/drain features which are located at two opposite sides of the first real gate portion to be spaced apart from each other in the X direction such that each of the first channel features interconnects the first source/drain features, the second device including a plurality of second channel features which extend away from the second wall surface and which are spaced apart from each other in the Z direction, a second real gate portion which is disposed around the second channel features, and two second source/drain features which are located at two opposite sides of the second real gate portion to be spaced apart from each other in the X direction such that each of the second channel features interconnects the second source/drain features, the third device including a plurality of third channel features which are spaced apart from each other in the Z direction, a third real gate portion which is disposed around the third channel features, and two third source/drain features which are

located at two opposite sides of the third real gate portion to be spaced apart from each other in the X direction such that each of the third channel features interconnects the third source/drain features; and forming an isolation feature on the substrate, the isolation feature extending in the Y direction through the first, second and third fins to permit the third device to be electrically isolated from the first and second devices.

16. The method of claim 15, wherein the third fin has a fin width in the Y direction which is greater than a fin width of each of the first and second fins in the Y direction.

17. The method of claim 15, wherein: the dielectric wall has an end surface interconnecting the first and second wall surfaces; the isolation feature includes a gate isolation portion; forming the first, second and third devices includes forming a first dummy gate portion disposed over the first and second fins and the dielectric wall, a second dummy gate portion disposed over the first, second and third fins, and a third dummy gate portion disposed over the third fin, the first, second and third dummy gate portions being spaced apart from each other in the X direction, and performing a replacement gate process such that the first dummy gate portion is replaced with a first gate structure including the first and second real gate portions, the second dummy gate portion is replaced with a second gate structure, and the third dummy gate portion is replaced with a third gate structure including the third real gate portion; and forming the isolation feature includes performing an etching process until the second gate structure is removed and portions of the first, second and third fins beneath the second gate structure are partially removed so as to form a trench which has a bottom at a level lower than a bottom surface of each of the first, second, and third source/drain features, and filling a dielectric material into the trench so as to form the gate isolation portion which is in direct contact with the end surface of the dielectric wall.

18. The method of claim 15, wherein: the dielectric wall has an end surface interconnecting the first and second wall surfaces; the isolation feature includes a gate isolation portion; and forming the first, second and third devices and the isolation feature includes forming a first dummy gate portion disposed over the first and second fins, a second dummy gate portion disposed over the first, second and third fins, and a third dummy gate portion disposed over the third fin, the first, second and third dummy gate portions being spaced apart from each other in the X direction, performing an etching process until the second dummy gate portion and portions of the first, second and third fins beneath the second dummy gate portion are partially removed so as to form a trench having a bottom at a level lower than a bottom surface of each of the first, second, and third source/drain features, filling a dielectric material into the trench so as to form the gate isolation portion which is in direct contact with the end surface of the dielectric wall, and performing a replacement gate process such that the first dummy gate portion is replaced with a first gate structure including the first and second real gate portions, and the third dummy gate portion is replaced with a second gate structure including the third real gate portion.

19. The method of claim 15, wherein: the dielectric wall has an end surface interconnecting the first and second wall surfaces; the isolation feature includes two gate isolation portions; forming the first, second and third devices includes forming first and second dummy gate portions disposed over the first and second fins and the dielectric wall, and third and fourth dummy gate portions disposed over the third fin, the first, second, third and fourth dummy gate portions being spaced apart from each other in the X direction, the second and third dummy gate portions being disposed between the first and fourth dummy gate portions, and performing a replacement gate process such that the first dummy gate portion is replaced with a first gate structure including the first and second real gate portions, the second and third dummy gate portions are respectively replaced with second and third gate structures, and the fourth dummy gate portion is replaced with a fourth gate structure including the third real gate portion; and forming the isolation feature includes performing an etching process until the second and third gate structures are removed, portions of the first and second fins beneath the second gate structure are partially removed, and a portion of the third fin beneath the third gate structure is partially removed so as to form two trenches each having a

bottom at a level lower than a bottom surface of each of the first, second, and third source/drain features, and filling a dielectric material into the trenches so as to respectively form the two gate isolation portions which are located at two opposite sides of the end surface of the dielectric wall.

20. The method of claim 15, wherein the isolation feature has a bottom surface at a level lower than a bottom surface of each of the first, second, and third source/drain features.
